C. Results of Standard Test Using Supported Heteropolyacid

Supported heteropolyacids are used as heterogenous catalysts in several industrial

2
NOV 06 1992

DOE/PC/90044--8

DE93 006476

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Received by OSTI

JAN 29 1993

Quarterly Technical Progress Report for the Period
July-September 1992

Kamil Klier and Richard G. Herman
with
Owen C. Feeley and Marie A. Johansson

Zettlemoyer Center for Surface Studies
and Department of Chemistry
LEHIGH UNIVERSITY
Bethlehem, PA 18015

October 1992

PREPARED FOR THE

U. S. DEPARTMENT OF ENERGY
PITTSBURGH ENERGY TECHNOLOGY CENTER

Contract No. DE-AC22-90PC90044

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED *Sc*

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States DOE, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

OBJECTIVES OF THE RESEARCH

The objective of the proposed research is to synthesize high octane ethers, primarily methyl isobutyl ether (MIBE) and methyl tertiary butyl ether (MTBE), directly from $H_2/CO/CO_2$ coal-derived synthesis gas *via* alcohol mixtures that are rich in methanol and 2-methyl-1-propanol (isobutanol). The overall scheme involves gasification of coal, purification and shifting of the synthesis gas, higher alcohol synthesis, and direct synthesis of ethers.

The last stage of the synthesis involves direct coupling of synthesis gas-derived methanol and isobutanol that has been demonstrated by us to occur over superacid catalysts to yield methyl isobutyl ether (MIBE) at moderate pressures and a mixture of methanol and isobutene at low pressures. MIBE is an isomer of MTBE and a process is proposed whereby MTBE from the two alcohols is maximized and MIBE is minimized. This will be achieved by the proper choice of reaction conditions, i.e. intermediate pressures, and of inorganic acid catalysts that are stable at temperatures higher than 200°C, at which the carbonium ion reaction coupling of the two alcohols to MTBE is more effective than the oxonium ion or ester reaction coupling to MIBE.

Both organic and inorganic catalysts will be investigated, and the better catalysts of these classes will be subjected to long term performance studies. The long term performance studies of the combined process will extend to 1000 hr and detailed analytical data for all products will be provided. The project is divided into the following three tasks:

Task 1. Synthesis of High Octane Ethers from Alcohol Mixtures Containing Predominantly Methanol and 2-Methyl-1-Propanol over Superacid Resins

Task 2. Inorganic Catalysts for the Synthesis of High Octane Ethers from Alcohols

Task 3. Long Term Performance and Reaction Engineering for Scale-Up of the Alcohols-to-Ethers Process

The expected result of the proposed research is a novel process for producing ethers, in particular MTBE, in which all five carbons of the unsymmetric C_1-O-C_4 ethers originate from coal-derived synthesis gas.

HIGH OCTANE ETHERS FROM SYNTHESIS GAS-DERIVED ALCOHOLS

SUMMARY OF TECHNICAL PROGRESS

Catalytic testing of inorganic catalysts was continued with the highly active sulfate-modified zirconia catalyst prepared here. Using isobutanol as the only reactant over this catalyst, it was demonstrated that high conversion and selectivity to isobutene was achieved at 175°C. In addition, the high selectivity to isobutene, i.e. 79-86 mol%, was maintained at higher space velocities and higher temperatures. A high productivity of 11.35 mol isobutene/(kg cat. hr) was achieved at 225°C with a flow rate of 20.28 mol isobutanol/(kg cat. hr). Utilizing a methanol/isobutanol = 2/1 molar ratio reactant mixture over the $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst, it was shown by a space velocity (contact time) study that the reaction conditions employed here fall in the differential reaction regime. In addition, it was found that the isobutene selectivity among the butenes produced hardly varied at a function of contact time and conversion level of isobutanol. This also indicated that the linear 2-butenes are primary products. In a separate study, it was shown that the yield of dimethylether increased as the pressure of methanol by itself was increased over the $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst, and these yields were higher than those in the presence of isobutanol.

A new supported heteropolyacid catalyst was prepared by supporting phosphotungstic acid ($\text{H}_3\text{PW}_{12}\text{O}_{40}$) on silica gel to the level of 20 wt%. It was shown that the same activities and selectivity patterns were obtained from methanol/isobutanol = 1/1 reactants whether the catalysts were calcined at 100°C or 200°C. It was shown that the activity and selectivity of these catalysts toward isobutene were increased by increasing the reaction temperature. However, under the set of reaction conditions employed, these catalysts were not better than the $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst.

TECHNICAL PROGRESS

A. Dehydration of Isobutanol Only Over $\text{ZrO}_2/\text{SO}_4^{2-}$

The activity and selectivity of dehydrating isobutanol over $\text{ZrO}_2/\text{SO}_4^{2-}$ in the absence of methanol was investigated. The preparation and calcination procedure for the sulfate modified zirconia are given in a previous report (1). The activity and selectivity of the catalysts for isobutanol dehydration were obtained with respect to reaction temperature and reactant space velocity.

Experimental

The $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst calcined to 620°C was placed in the reactor of the previously described gas phase flow reactor system. The following reaction conditions were utilized during the course of the investigation:

Temperature	125, 135, 150, 175, 200, 225°C
Pressure	1 atm
Isobutanol feed	1.69-20.28 mol/kg catalyst/hr
He + N_2 flow	18.78 mol/kg catalyst/hr
Catalyst weight	5.0 g.

The isobutanol space velocity of 1.69 mol/(kg cat. hr) was used in an initial temperature dependence study from 125 to 175°C . At the temperature of 200°C , the isobutanol flow rate was raised sequentially to 6.76, 13.52, and 20.28 mol/(kg cat. hr). A final test was performed at 225°C using 20.28 mol/(kg cat. hr) of isobutanol. Testing was carried out for several hours at each point of temperature and space velocity. The only major products observed with the on-line GC analysis were isobutene, *trans*-2-butene, and *cis*-2-butene. Trace amounts of octenes and C_8 ethers were seen. At higher reaction temperatures, methanol and other products believed to be cracking products of isobutanol were seen as was observed for isobutanol only dehydration over H-mordenite (2). The yields of the major

products under these conditions are presented in Figures 1A-1C. It can be seen that the predominant product was isobutene in each case and that high activity was achieved at 175°C while maintaining the high selectivity to isobutene (Figure 1A). As the temperature was increased from 125°C to 175°C, the total isobutanol conversion progressively increased from 13 to 85 mol% while the isobutene selectivity varied from 86 to 79 mol%. Increasing the space velocity of the isobutanol (Figure 1B) increased the yield of isobutene while also maintaining the isobutene selectivity at 80-81 mol%. The highest productivity of isobutene of 11.35 mol/(kg cat. hr) was obtained at 225°C and a flow rate of 20.28 mol isobutanol/(kg cat. hr), as shown in Figure 1C. In this case, the selectivity of isobutene among the butenes at this high productivity was 79%. This space time yield can be compared with the highest reported value of isobutanol production from synthesis gas in the literature that is claimed to be 10 mol/(kg cat. hr) (3). Thus, the dehydration of isobutanol to isobutene would not be a limiting step in an overall process of converting synthesis gas to MTBE.

B. Reaction of Methanol/Isobutanol Mixture over $\text{ZrO}_2/\text{SO}_4^{2-}$ vs Contact Time

The kinetic studies of the methanol (MeOH)/isobutanol (i-BuOH) reaction over $\text{ZrO}_2/\text{SO}_4^{2-}$ presented in the last quarterly report (4) are complemented with a study investigating the effect of contact time on the conversion and selectivity of the major reactions. The following conditions were used in these studies:

Temperature	157°C
Pressure (total)	1 atm
Methanol feed	13.8-123.3 mol/kg catalyst/hr
Isobutanol feed	6.92-61.6 mol/kg catalyst/hr
He (+ N ₂ trace) flow	245.2-2,207 mol/kg catalyst/hr
Catalyst weight	0.25 g.

The reactant mixture was a 2/1 molar MeOH/i-BuOH mixture, and the partial pressure of the alcohols was kept constant throughout the experiment by altering the space velocity of

FIGURE 1A
REACTION OF ISOBUTANOL
(1.69 mol/(kg cat*hr)) OVER $\text{ZrO}_2/\text{SO}_4^{2-}$

FIGURE 1B
REACTION OF ISOBUTANOL AT 200°C
vs SPACE VELOCITY OVER $\text{ZrO}_2/\text{SO}_4^{2-}$

FIGURE 1C
REACTION OF ISOBUTANOL AT
20.69 mol/(kg cat*hr) OVER $\text{ZrO}_2/\text{SO}_4^{2-}$

the inert gas feed (containing N_2 as an internal standard) proportionally to that of the alcohols. In the usual manner, a fresh ZrO_2/SO_4^{2-} sample calcined to $620^\circ C$ was charged into the reactor, the gas flow rates were adjusted, and the reactor was brought to the reaction temperature. The experiment started with the highest space velocities, which were sequentially lowered. Product analysis at each space velocity was the average of multiple sampling at each point. The contact times were defined as $1/GHSV$; where the space velocity had been converted from mol reactant/(kg cat. hr) to STP liter of reactant gas/(liter catalyst $\times$ min) *via* the ideal gas equation and assuming that the volume of 1 kg catalyst = 1 liter.

Figure 2 shows the percent conversion of isobutanol vs the contact time of the isobutanol in the catalyst. A linear relationship exists over the entire range tested, indicating that reaction studies within this range of contact times are within the kinetic regime. The kinetic data presented in the last quarterly report lie well within the bounds of the kinetic regime, thus establishing that kinetic interpretation of that data is valid.

The butene product selectivity as a function of contact time is presented in Figure 3. It is clear that isobutene is the predominant butene formed, and it is produced at a higher percentage, i.e. 86-88 mol%, than that calculated for thermodynamic equilibrium, ca. 70%, at the reaction temperature of $157^\circ C$. It is also interesting to note that the selectivity of *cis*-2-butene is now comparable to, or even greater than, that of the *trans*-2-butene product, in contrast to the relative yields expected from equilibrium considerations (4). In addition, the composition of butenes with respect to selectivity remains constant over the range of contact times, and thus conversion levels of isobutanol, studied. This indicates that the linear butenes are also primary products and not the result of secondary isomerization of the isobutene produced in the reaction, in accordance with other studies (5).

FIGURE 2

Contact Time Dependence at 157°C
2:1 MeOH:i-BuOH Mixture over $\text{ZrO}_2/\text{SO}_4^{2-}$

FIGURE 3
BUTENE PRODUCT SELECTIVITY AT 157°C FOR
ISOBUTANOL DEHYDRATION OVER $\text{ZrO}_2/\text{SO}_4^{2-}$

C. Results of Standard Test Using Supported Heteropolyacid

Supported heteropolyacids are used as heterogenous catalysts in several industrial applications. They are reported to possess strong acidic character, as well as unique selectivity characteristics. The use of silica-supported phosphotungstic acid, designated herein as $\text{PW}_{12}/\text{SiO}_2$, for the standard reaction of a 1/1 molar MeOH/i-BuOH mixture was investigated.

Preparation

Phosphotungstic acid with a formula of $\text{H}_3\text{PW}_{12}\text{O}_{40}$ was obtained from Fisher Scientific. Silica gel was obtained from Davison and had the following properties: Davisil grade 646, 35-60 mesh, surface area = $300 \text{ m}^2/\text{g}$, pore volume = $1.15 \text{ cm}^3/\text{g}$, and 150 Å pore size. An aqueous solution consisting of 5 g of phosphotungstic acid in 23 ml of distilled water was prepared. A 20 g portion of the silica was impregnated with this solution, with constant mixing, to make a 20% loading of phosphotungstic acid by weight. The impregnated silica, $\text{PW}_{12}/\text{SiO}_2$, was placed in a 100°C oven overnight. A sample of this material calcined to 200°C was also prepared. These calcination temperatures were chosen because they are below the decomposition range reported for heteropolyacids.

The samples were charged to the reactor in the usual manner, and the following reaction conditions were used:

Temperature	90, 125, 150, 175°C
Pressure	1 atm
Methanol feed	$1.72 \text{ mol/kg catalyst/hr}$
Isobutanol feed	$1.72 \text{ mol/kg catalyst/hr}$
He + N_2 flow	$16.0 \text{ mol/kg catalyst/hr}$
Catalyst weight	5.0 g.

The results, presented as the space time yields of the major products as a function of reaction temperature, are given in Figures 4 and 5 for the catalysts prepared at the 100 and

FIGURE 4
PW₁₂/SiO₂ Calcined @ 100°C
MeOH/i-BuOH = 1/1

FIGURE 5
PW₁₂/SiO₂ Calcined @ 200°C
MeOH/i-BuOH = 1/1

200°C calcination temperatures. The results are identical for the two catalyst samples. No activity was found at a reaction temperature of 90°C. The activity and selectivity was comparable with the silica-alumina catalyst tested previously (1,6), with isobutene being the most selective product at 175°C. However, the $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst remains as the most active and selective of all catalysts in the standard test screenings for the reaction of the MeOH/i-BuOH mixture (1,6). The presence of t-BuOH indicates that some of the isobutene product had been hydrated over this catalyst.

D. Determination of Acidity via Aqueous Titration of $\text{ZrO}_2/\text{SO}_4^{2-}$

Characterization of the promising $\text{ZrO}_2/\text{SO}_4^{2-}$ catalyst was continued, and this included an attempt to determine the number of acid sites in terms of milliequivalents per gram of catalyst, i.e. meq/g. The concentration of sulfur had been previously determined, *via* elemental analysis, to be 2.6 and 3.0 mmol/g for two separate preparations (4). Calcined $\text{ZrO}_2/\text{SO}_4^{2-}$ is known to possess both Lewis and Bronsted acidic sites. However, in our reactions of interest, water is always the predominant product and Lewis sites are converted to Bronsted sites under such conditions (7). In this study, a suspension of $\text{ZrO}_2/\text{SO}_4^{2-}$ in water, as well as a Na^+ ion-exchanged sample, were titrated with standardized solutions of NaOH to determine the acidic content of the catalyst.

Experimental

A Markson model 88 pH meter was used for determination of pH during the titration experiments. The NaOH solutions were standardized against known amounts of potassium hydrogen phthalate from Aldrich. In the first experiment, a 2.3095 g sample of $\text{ZrO}_2/\text{SO}_4^{2-}$ previously calcined to 620°C and containing 3.0 mmol S/g was suspended in *ca.* 40 ml of distilled water. The electrode of the calibrated pH meter was immersed in the aqueous

suspension to be titrated. Small volumetric additions from a buret containing 0.07965 N NaOH solution were added to the suspension while recording both the volume of NaOH solution added and the resultant pH of the aqueous suspension. It was noticed that long equilibration times were necessary following NaOH additions, i.e. 1-2 hr. When the titration was close to the neutralization point, i.e. pH of 7, the beaker containing the suspension was covered tightly with parafilm and stirred for three days to equilibrate. Following this period, the titration was continued. In total, 8.17 ml of 0.07965 N NaOH solution were needed to neutralize the suspension with the 2.3095 g sample of $\text{ZrO}_2/\text{SO}_4^{2-}$. The following calculation determines the number of acid sites titrated in the experiment:

$$8.17 \text{ ml} \times (0.07965 \text{ meq/ml}) \times (1/2.3095 \text{ g}) = 0.28 \text{ meq/g}$$

In light of the extensive equilibration times necessary to achieve stable pH readings in the above experiment, an alternative method of acid site determination was utilized. Forni described the method of adding excess NaCl to exchange with H^+ on the surface of catalysts in cases of long equilibration titrations (8). The HCl solution thus formed is easily titrated with base. Approximately 30 ml of a 5% NaCl solution by weight was added to 2.3036 g of $\text{ZrO}_2/\text{SO}_4^{2-}$, and this was allowed to stir overnight. The solution was then titrated with 0.1051 N NaOH solution while measuring its pH with the meter. With this method, equilibration was fast, within about a minute at each point. The total volume of 0.1051 N NaOH needed to neutralize the HCl solution was 6.3 ml. The acidity of the $\text{ZrO}_2/\text{SO}_4^{2-}$ was determined to be:

$$6.30 \text{ ml} \times (0.1051 \text{ meq/ml}) \times (1/2.3036 \text{ g}) = 0.29 \text{ meq/g}$$

This is approximately the same value as that found for the direct titration of the aqueous suspension. As the concentration of sulfur, existing as SO_4^{2-} , was 0.3 mmol/g, it appears that there is one Bronsted acid site, under wet conditions, for each sulfate group

on the surface. This result indicated that sulfuric acid, which would have two Bronsted protons per sulfate, is not reformed by the addition of water to the catalyst.

E. Pressure Dependence on Methanol Dehydration

To complete the alcohol pressure dependence study on sulfate-modified zirconia, methanol was utilized as the reactant in the absence of isobutanol. The following experimental conditions were used:

Temperature	157°C
Pressure (total)	1-7 MPa
Methanol feed	42.2 mol/kg cat/hr
He (+ N ₂ trace)	776.4 mol/kg cat/hr
Catalyst weight	0.40 g

Figure 6 presents the space time yield of dimethyl ether (DME). It is clear that increasing the methanol pressure favors an increase in the dimethylether (DME) formation rate. The yield of DME is in general higher when no competition with isobutanol is present. Upon returning to the original partial pressure of methanol, only minor deactivation of the catalyst was seen.

F. Nafion-H MS Activity Dependence on Sodium Content

The objective was to study the role that the number of acid sites has on the activity of the Nafion-H MS catalyst.

Sample Preparation

To 0.52 g of Nafion-H MS was added 5.2 ml of 0.016 M sodium chloride solution. Since Nafion-H MS has 0.89 meq H⁺/g, the added sodium chloride corresponded to 18% of the acid sites. The catalyst was left to equilibrate with the NaCl solution overnight. The pH was measured before and after equilibration, and the difference was taken to correspond to the amount of sodium exchanged into the Nafion-H MS catalyst. The experimental value

FIGURE 6
Methanol Over $\text{ZrO}_2/\text{SO}_4^{2-}$ at 157°C
Total Pressure Range = 1-7 MPa

of exchange was 18%. The catalyst was then washed in distilled water until a neutral pH was obtained. Following this, the sample was filtered, dried at 100°C for 3 hr, and then left to cool in air. The following experimental conditions were used for the testing of the non-exchanged catalyst and for the Na⁺ exchanged sample:

Temperature	90°C
Pressure	1 atm
Methanol feed	5.7 mol/kg cat/hr
Isobutanol feed	5.7 mol/kg cat/hr
Helium (+ N ₂ trace)	52.7 mol/kg cat/hr
Catalyst weight	0.5 g

Table 1 shows that both the non-exchanged and the 18% exchanged Nafion-H MS produced three major products, e.g. MIBE, DME and isobutene. In both cases, MIBE was the dominant product. The yield of MIBE only decreased 10% with the sample having 18% less acidic sites available.

Table 1. Yield of Non-exchanged and 18% Exchanged Nafion-H MS

Compound	Yield non-exchanged (mol/kg cat/hr)	Yield 18% exchanged (mol/kg cat/hr)
MIBE	0.050	0.045
DME	0.015	0.015
Isobutene	0.009	0.013

It is known from previous experiments that 100% exchange of Nafion-H with potassium resulted in a 100% activity loss (1). Figure 7 shows the relationship between the amount of sodium exchanged and the yield of MIBE. Further experiments are needed to establish if this is a linear relationship or if there is a critical drop in activity when the sodium content is increased.

FIGURE 7
Yield of MIBE versus Sodium Content

G. MIBE Synthesis

Methyl isobutyl ether (MIBE) was synthesized using the Williamson ether synthesis (9). The preparation involves the formation of sodium butoxide from metallic sodium and isobutanol. Methyl iodide was added to form MIBE and sodium iodide. The resulting MIBE was 97% pure after distillation as determined by gas chromatography. A 140 ml portion of MIBE was sent to Southwest Research Institute (SRI) for evaluation of the cetane number.

References

1. Klier, K., Herman, R. G., Johansson, M., and Feeley, O. C., *Quarterly Technical Progress Report* DOE/PC/90044-5, 25 pp (January 1992).
2. Klier, K., Herman, R. G., Johansson, M. A., and Feeley, O. C., *Quarterly Technical Progress Report* DOE/PC/90044-6, 23 pp (April 1992).
3. Keim, W., and Falter, W., *Catal. Letters*, 3, 59 (1989).
4. Klier, K., Herman, R. G., Feeley, O. C., and Johansson, M. A., *Quarterly Technical Progress Report* DOE/PC/90044-7, 16 pp (July 1992).
5. Kotsarenko, S., and Malysheva, L.V., *Kinet. Katal.*, 24, 877 (1983).
6. Klier, K., Herman, R. G., Johansson, M. A., and Feeley, O. C., *Preprints, Div. Fuel Chem., ACS*, 37(1), 236 (1992).
7. Arata, K. *Adv. Catal.*, 37, 165 (1990).
8. Forni, L. *Catal. Rev.*, 8(1), 65, (1973).
9. Klier, K., Herman, R. G., Bastian, R. D., and DeTavernier, S., *Quarterly Technical Progress Report* DOE/PC/90044-1, 44 pp (January 1991).

END

DATE
FILMED
3/19/93