WSRC-TR--92-346

DE93 002808

Keywords: glass, DWPF,
durability standard, redox standard,
chemical standard

CHARACTERIZATION OF THE DEFENSE WASTE PROCESSING FACILITY (DWPF) ENVIRONMENTAL ASSESSMENT (EA) GLASS STANDARD REFERENCE MATERIAL (U)

C. M. JANTZEN, N.E. BIBLER, AND D.C. BEAM

Approved by

**E.W. Holtzscheiter, Research Manager
Defense Waste Processing Technology**

Publication Date: September 30, 1992

Authorized Derivative Classifier

**Westinghouse Savannah River Co.
Savannah River Site
Aiken, SC 29808**

**PREPARED FOR THE U.S. DEPARTMENT OF ENERGY UNDER
CONTRACT DE-AC09-89SR18035**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This page intentionally left blank.

ABSTRACT

Liquid high-level nuclear waste at the Savannah River Site (SRS) will be immobilized by vitrification in borosilicate glass. The glass will be produced and poured into stainless steel canisters in the Defense Waste Processing Facility (DWPF). Other waste form producers, such as West Valley Nuclear Services (WVNS) and the Hanford Waste Vitrification Project (HWVP), will also immobilize high-level radioactive waste in borosilicate glass. The canistered waste will be stored temporarily at each facility for eventual permanent disposal in a geologic repository. The Department of Energy has defined a set of requirements for the canistered waste forms, the Waste Acceptance Preliminary Specifications (WAPS). The current Waste Acceptance Preliminary Specification (WAPS) 1.3, the product consistency specification, requires the waste form producers to demonstrate control of the consistency of the final waste form using a crushed glass durability test, the Product Consistency Test (PCT). In order to be acceptable, a waste glass must be more durable during PCT analysis than the waste glass identified in the DWPF Environmental Assessment (EA). In order to supply all the waste form producers with the same standard benchmark glass, 1000 pounds of the EA glass was fabricated. The chemical analyses and characterization of the benchmark EA glass are reported. This material is now available to act as a durability, analytic, and/or redox Standard Reference Material (SRM) for all waste form producers.

This page intentionally left blank.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	3
INTRODUCTION	7
EXPERIMENTAL	8
Glass Fabrication	8
Glass Sampling	8
Glass Composition Analyses	8
Glass Viscosity Analyses	10
Glass Homogeneity Analyses	10
Glass Durability Analyses	10
QUALITY ASSURANCE	11
RESULTS AND DISCUSSION	13
Glass Composition Analyses	13
Glass Viscosity Analyses	16
Glass Homogeneity Analyses	17
Glass Durability Analyses	17
Multielement Standard Analysis	17
Standard Glass Analysis	17
EA Glass Analysis	17
CONCLUSIONS	23
ACKNOWLEDGEMENT	23
REFERENCES	25

TABLE OF CONTENTS (Continued)

	<u>Page</u>
APPENDIX I	29
APPENDIX II	35
APPENDIX III	45

CHARACTERIZATION OF THE DEFENSE WASTE PROCESSING FACILITY (DWPF) ENVIRONMENTAL ASSESSMENT (EA) GLASS STANDARD REFERENCE MATERIAL (U)

INTRODUCTION

Waste form producers at the Savannah River Site (SRS), West Valley Nuclear Services (WVNS), and Hanford Waste Vitrification Project (HWVP) will immobilize high-level radioactive waste in borosilicate glass. The glass will be poured into stainless steel canisters for eventual disposal in a geologic repository. The Department of Energy has defined a set of requirements for the canistered waste forms, the Waste Acceptance Preliminary Specifications (WAPS).¹

The current Waste Acceptance Preliminary Specification (WAPS) 1.3, the product consistency specification, requires the waste form producers to demonstrate control of the consistency of the final waste form using the Product Consistency Test (PCT).²⁻⁵ The PCT is a crushed glass durability test which is (1) sensitive to glass composition and homogeneity, and (2) may have the potential to be related to repository site-specific release tests. It is a glass dominated production test which can be used to test glasses during production, even in the shielded cell environments necessitated by highly radioactive glasses.²⁻⁷ A standard glass is always measured simultaneously to an unknown during PCT analysis.

The WAPS 1.3 specification defines the acceptance criterion for a production glass: a waste glass being produced must be more durable during PCT analysis than the waste glass identified in the DWPF Environmental Assessment (EA).⁸ During simultaneous PCT analysis of the production glass and the EA glass, the latter can be used as the standard glass required by the PCT protocol.

The WAPS 1.1.2 requires that the waste form producers report the measured chemical composition of the glass waste form in the Production Records. The Defense Waste Processing Facility (DWPF) process/product models relate important processing and product quality requirements to glass composition.⁹ Routine chemical analyses of vitrified feed samples is required. In addition, control of the oxidation/reduction (redox) equilibrium in the glass melter is critical for processing of the nuclear waste.¹⁰⁻¹⁵ As part of the DWPF process control strategy, the glass redox expected in the melter will be determined by measuring the ratio of $\text{Fe}^{2+}/\Sigma\text{Fe}$ in vitrified slurry.¹⁶⁻¹⁷ Routine redox analyses of vitrified feed samples is required. A glass standard with a known redox and composition, such as the EA glass, will need to be run simultaneously with the production glass or vitrified feed in order to minimize error and long term instrumental bias.^{18, 19}

In order to supply the DWPF and all the waste form producers with the same standard benchmark glass, the Savannah River Technology Center (SRTC) had 1000 pounds of the EA glass fabricated by Corning Glass Works (AX-AA28362A). The chemical analyses and characterization of the benchmark EA glass, to be used as a durability, analytic, and/or redox Standard Reference Material, are reported in this study.

EXPERIMENTAL

Glass Fabrication

The composition of the glass as given in the DWPF Environmental Assessment⁸ is shown in Table 1. The target composition of the glass to be fabricated is also given in Table 1. The target EA glass composition was derived from the composition given in the EA⁸ by the following calculational procedure:

- recalculating the MnO_2 as MnO due to the reduced nature of this glass
- recalculating the Fe_3O_4 as Fe_2O_3 and FeO
- calculating "other solids" as primarily zeolite²⁰
- deleting the U_3O_8 component due to the difficulty of handling and shipping uranium bearing glass as a Standard Reference Material
- normalizing to 100 wt%

Corning Glass Works fabricated the glass in a gas fired atmospheric furnace with an oxygen:natural gas mixture of 2:1 to control the redox of the atmosphere. The iron was added as ferric iron oxide (Fe_2O_3) and ferrous iron oxalate dihydrate ($\text{FeC}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$). Five pounds of carbocite carbon were added per master batch of 1203 pounds of glass to reduce the glass during melting and to be able to control the redox with the gas mixture more efficiently. The batch was melted at 1250°C and N_2 was bubbled through the batch to assist in homogenizing the glass. The glass was kept at 1100°C while it was being drained and water quenched to ensure that devitrification did not occur. The glass melt adsorbed water during quenching and was air dried in a Peterson Kelly (PK) blender to prevent particle agglomeration.

Glass Sampling

The glass was received in three large drums. A stainless steel tube of ~1/2 inch diameter was used under vacuum to sample glass from the bottom, middle, and top of each drum. A similar technique had been used at Corning Glass Works for glass sampling after fabrication.

Glass Composition Analyses

Corning Glass Works analyzed five samples of the EA glass after fabrication. Each sample was dissolved in triplicate. The fifteen dissolutions were analyzed in duplicate for Al, B, Ca, Fe, K, La, Li, Mg, Mn, Na, Ni, Si, Ti, Zr, and $\text{Fe}^{2+}/\text{Fe}^{3+}$ on different days to include any short time instrumental bias in the measurement of the standard deviation. The average and standard deviation of the 30 replicate EA glass analyses measured by Corning Glass Works is given in Table 1. Details of the analyses are given in Appendix I.

Table 1. Comparison of EA Glass Composition, Target Glass Composition, and Corning Glass Works Analyzed Glass Composition

	EA Glass Composition	Target Glass Composition	Corning Glass Works Analyzed Glass Composition*	SRS Analyzed Glass Composition
Al ₂ O ₃	3.2	3.67 ± 0.18 ^t	3.70 ± 0.023	3.60±0.12
B ₂ O ₃	10.9	11.12 ± 0.556 ^t	11.3 ± 0.097	11.16± 0.17
CaO	1.0	1.13 ± 0.06 ^t	1.12 ± 0.007	1.23± 0.09
Fe ₂ O ₃	5.9	8.08 ± (see redox) [‡]	7.38 ± 0.074	7.58 ± 0.41
FeO		0.89 ± (see redox) [‡]	1.45 ± 0.041	1.59 ± 0.06
Fe ₃ O ₄	2.8			
K ₂ O		0.04 ± 0.004	0.04 ± 0.000	0.04 ±0.01
La ₂ O ₃	0.4	0.41 ± 0.04	0.42 ± 0.005	0.28 ±0.02
Li ₂ O	4.2	4.28 ± 0.21 ^t	4.26 ± 0.015	4.21 ± 0.15
MgO	1.6	1.66 ± 0.08 ^t	1.72 ± 0.011	1.79 ± 0.07
MnO		1.34 ± 0.07 ^t	1.34 ± 0.01	1.36 ± 0.05
MnO ₂	1.6			
Na ₂ O	16.3	16.71 ± 0.84 ^t	16.8 ± 0.061	16.88 ± 0.32
NiO	0.6	0.61 ± 0.06	0.57 ± 0.005	0.53 ± 0.03
SiO ₂	46.3	48.95 ± 4.90	48.73 ± 0.302	48.76 ± 0.82
TiO ₂	0.7	0.71 ± 0.07	0.70 ± 0.006	0.65 ± 0.03
U ₃ O ₈	1.2			
ZnO				0.26 ± 0.04
ZrO ₂	0.4	0.41 ± 0.04	0.46 ± 0.012	0.48 ± 0.08
Other Solids ^{tt}	<u>2.9</u>			
SUM	100.00	100.01	99.99	100.41
Fe ²⁺ /Fe ³⁺	0.123	0.1 to 0.3	0.22±0.01	0.23 ± 0.01

* average and standard deviation of 30 replicate analyses are given in Appendix I

tt where other solids include zeolite, undissolved salts, and radionuclides (<0.1% of the waste)⁸

t corresponds to 5 relative wt%, all others are 10 relative wt%

‡ values based on Fe²⁺/Fe³⁺=0.123; actual values vary on exact ratio of Fe²⁺/Fe³⁺ achieved between the specified range of 0.1 to 0.3

The Analytic Development Section of the Savannah River Technology Center analyzed ten samples of the EA glass and two Purex glass standards to determine the glass composition. Twelve samples of the EA glass were measured for redox. The EA glass samples were analyzed by the following techniques:

- Dissolution by Na_2O_2 with an HCl uptake
 - ICP for Al, Si, B
- Dissolution by HCl/HF microwave
 - ICP for Na, Zr, Ca, Fe, Mg, Mn, Li, Cr, Sr, Ti, P, Ba, Pb, Mo, Zn, Cu, Ni, La
 - AA for Na, K, Cs
- Dissolution by Na_2O_2 with a H_2O uptake
 - IC for SO_4 , NO_3 , and PO_4
 - ISE for Cl and F
- Dissolution by $\text{H}_2\text{SO}_4/\text{HF}$ in the presence of $\text{NH}_4\text{VO}_3^{21}$
 - Colorimetric for Fe^{2+} and total Fe (ΣFe)

where ICP is Inductively Coupled Plasma Spectroscopy, AA is Atomic Absorption analysis, IC is Ion Chromatography analysis, and ISE is Ion Selective Electrode analysis.

Glass Viscosity Analyses

A five-point high temperature viscosity analysis was performed on a Brookfield Viscometer according to ASTM-C-965A by Sharp-Schurtz Analytical Division of Owens/Corning Fiberglas Corporation.

Glass Homogeneity Analyses

X-ray Diffraction (XRD) and Scanning Electron Microscopy (SEM) analyses coupled with Energy Dispersive Analysis by X-ray (EDAX) were performed on the EA glass in order to determine the crystallinity and/or homogeneity of the glass.

Glass Durability Analyses

The durability of the EA glass was examined using Version 3.0 of the PCT.³ In the PCT analysis, crushed glass of 100-200 mesh is immersed in ASTM Type I water for 7 days at 90°C. The surface area of the glass exposed in 100-200 mesh glass can be calculated using an assumed waste glass density (~2.76 g/cc for average SRS glasses) and by assuming a Gaussian distribution of particle sizes. Since the volume of leachant solution (V) is maintained at 10 mL per gram of glass, the ratio of the glass surface area (SA) to the volume (V) of leachant is 19.55 cm^{-1} . PCT leachates were filtered to remove colloids and/or particulates. The leachates were analyzed for pH and the elemental concentration of the glass species of interest.

Three researchers completed PCT analysis of the EA glass. The first researcher completed triplicate analyses of two EA glass samples in 60 mL 75 psi Teflon® vessels. The second researcher completed six replicate PCT analyses of one EA glass sample in the same type of Teflon® vessel. The third researcher completed quadruplicate PCT analyses of one EA glass sample in the same type of Teflon® vessels. The third researcher also ran two sets of quadruplicate PCT analyses of the EA glass in 22mL 304L stainless steel Parr bombs with a well polished surface interior finish. One set of tests in the steel vessels used 19 mL of ASTM-Type I water leaving zero head space for air in the vessel. The second set of PCT analyses was performed on the EA glass in the 22mL Parr bombs with only 15mL of ASTM-Type I water leaving 4 mL head space for air in the vessel.

A standard glass, ARM-1 was used by all the researchers to ascertain if long term bias in the experimental analysis had occurred compared to previous glasses tested at SRS. Replicate PCT tests on the EA glass and on the glass standards were run simultaneously.

A multielement solution standard was used by all the researchers to ensure that instrumental drift in the Inductively Coupled Plasma (ICP) Spectroscopy and/or Atomic Absorption (AA) analyses did not bias the short term leachate analyses. Duplicate durability tests containing ASTM Type I water but no glass samples were run simultaneously with each set of samples as "blanks." All conditions, including the type of vessel and the head space in the vessel were kept the same for the blank tests and the EA glass tests. The use of blanks ensures that the test vessel preparation was adequate and that the sample leachates can be corrected for elemental variation occurring independently of the glass-solution interactions.

QUALITY ASSURANCE

All melting and glass analyses performed at Corning Glass Works were carried out in accordance with RW-0214 and NQA-1. All glass physical property measurements performed at Owens Corning Fiberglas were carried out in accordance with RW-0214 and NQA-1. All glass analyses performed at the Savannah River Technology Center were carried out in accordance with RW-0214 and NQA-1. The data for the chemical analyses performed at Corning Glass Works and at SRS are recorded in WSRC-NB-91-237 and WSRC-NB-92-129. The XRD, SEM, EDAX analyses performed at SRS and the viscosity analyses performed at Owens Corning Fiberglas are recorded in the same notebook. The glass durability data of the first and second researchers is recorded in WSRC-NB-91-199 and WSRC-NB-91-200, respectively. The data of the third researcher is recorded in DPSTN-4793.

This page intentionally left blank.

RESULTS AND DISCUSSION

Glass Composition Analyses

Ten replicates of the EA glass were analyzed chemically at the Savannah River Technology Center. Detailed results for each analysis are given in Appendix II. Duplicate analyses of a glass standard from the Waste Compliance Plan,²² the WCP Purex glass, were run simultaneously. The analysis included a redox measurement so that the total Fe could be speciated as Fe_2O_3 and FeO . The analytic values for Al_2O_3 , SiO_2 , and Na_2O were biased low compared to the standard Purex glass analysis. An average bias correction for these oxides were calculated from the duplicate Purex glass analyses and applied to the analyses of the ten replicate EA glass samples (Appendix II). The average oxide wt% bias for Al_2O_3 ranged from 4 to 6.7, while the average bias for SiO_2 and Na_2O ranged from 1.5 to 2.9 and 4.3 to 4.4, respectively. The average oxide wt% bias corrections used were 5, 2, and 4 for Al_2O_3 , SiO_2 , and Na_2O , respectively.

The bias corrected analyses for the ten replicate EA glass samples is given in Table 2 with the Fe speciated as Fe_2O_3 and FeO based on the measured redox which is also given in Table 2. The composition of the 1000 pounds of EA glass, including the redox, appears to be homogeneous: there are no chemical differences between the glass samples from the three drums, nor from the glass sampled from the top, middle, or bottom of each drum.

The average composition and the standard deviations of the EA glass composition measurement at SRTC are also given in Table 2. These values are compared to the target glass analyses and to the Corning Glass Works composition in Table 1. One sample from drum two (2-MISC) appears to be significantly different than the other analyses in terms of its Fe_2O_3 , B_2O_3 , and SiO_2 content. Although this analysis is considered deviate, the average and standard deviations given in Table 2 are based on all ten replicate analyses.

Within the standard deviations of the replicate analyses of both laboratories the analyses verify that the 1000 pounds of EA glass is within the target glass composition specified. The redox analyses measured by SRTC agree to within 0.01 of the values measured by Corning Glass Works. The SRTC analyses agree closely with the Corning Glass Works analyses except for minor component and anion analysis, e.g. La_2O_3 , ZnO , Cl , and F . The SRTC values for La_2O_3 are lower than the values reported by Corning Glass Works by ~33%. In addition SRTC determined the presence of ZnO and trace amounts of Cl ($\sim 0.10 \pm 0.05$ wt%) and F ($\sim 0.008 \pm 0.005$ wt%). The presence of the ZnO impurity was ascertained from glasses that were dissolved in microwave Teflon[®] bombs. Therefore, the presence of the trace ZnO is not due to impurities in the dissolution vessel as observed when samples are dissolved in nickel or zirconia crucibles.²³ The Cl and F analyses have large standard deviations since the values measured are close to the detection limits of the measurement technique.

The EA glass is homogeneous and suitable as a compositional, redox, and durability Standard Reference Material despite the minor differences between the SRTC and Corning Glass Works analyses for La_2O_3 and ZnO . The presence of trace amounts of anions is not significant because the analytic determinations were so close to the detection limits of the instrumentation.

Table 2. Replicate Analyses of the Environmental Assessment Glass

OXIDE WT%	SAMPLE AND ANALYTIC IDENTIFICATIONS					
	1-TOP-A	2-TOP-A	3-TOP-A	1-MISC-A	2-MISC	3-MISC-A
	#200074772	#200074773	#200074774	#200074770	#200074777	#200074771
	#200074760	#200074761	#200074762	#200074763	#200074764	#200074765
	#200080110	#200080111	#200080112	#200080113	#200080114	#200080115
	#200080136	#200080128	#200080129	#200080130	#200080131	#200080132
Al ₂ O ₃	3.58	3.67	3.77	3.54	3.80	3.46
B ₂ O ₃	11.12	11.32	11.22	11.32	10.76	11.12
CaO	1.20	1.22	1.22	1.23	1.15	1.20
Fe ₂ O ₃	7.47	7.49	7.48	7.43	8.30	7.33
FeO	1.59	1.57	1.69	1.60	1.61	1.50
K ₂ O	0.04	0.06	0.04	0.04	0.04	0.04
La ₂ O ₃	0.27	0.28	0.28	0.27	0.26	0.26
Li ₂ O	4.19	4.24	4.28	4.19	4.02	4.13
MgO	1.77	1.79	1.81	1.78	1.72	1.76
MnO	1.35	1.37	1.38	1.36	1.32	1.33
Na ₂ O	16.86	17.03	17.33	16.90	16.37	16.75
NiO	0.52	0.52	0.54	0.54	0.50	0.50
SiO ₂	49.03	49.18	48.36	49.34	48.37	47.81
TiO ₂	0.64	0.65	0.66	0.64	0.62	0.63
ZnO	0.25	0.24	0.24	0.25	0.25	0.24
ZrO ₂	0.48	0.48	0.46	0.44	0.70	0.42
 OXIDE SUMS	 100.38	 101.11	 100.77	 100.87	 99.8	 98.48
Fe ²⁺ /Fe ³⁺	0.24	0.23	0.25	0.24	0.22	0.23
 ANION WT%						
Cl	0.086	0.095	0.094	0.114	0.142	0.090
F	0.006	0.005	0.013	0.003	0.005	0.004

Table 2. Replicate Analyses of the Environmental Assessment Glass (Cont'd)

OXIDE WT%	SAMPLE AND ANALYTIC IDENTIFICATIONS				AVERAGE	STD DEV	CORNING'S GLASS ANALYSIS
	1-B-3	2-B-A	2-M-1	2-M-3			
	#200074778-80	#200074781	#200074775	#200074776			
	#200074766	#200074767	#200074768	#200074769			
	#200080116	#200080117	#200080118	#200080119			
	#200080133	#200080134	#200080135	#200080136			
Al ₂ O ₃	3.43	3.55	3.55	3.64	3.60	0.12	3.70
B ₂ O ₃	11.08	11.16	11.18	11.33	11.16	0.17	11.30
CaO	1.25	1.15	1.24	1.48	1.23	0.09	1.12
Fe ₂ O ₃	7.29	7.02	7.76	8.26	7.58	0.41	7.38
FeO	1.63	1.61	1.51	1.60	1.59	0.06	1.45
K ₂ O	0.04	0.04	0.03	0.04	0.04	0.01	0.04
La ₂ O ₃	0.30	0.28	0.28	0.33	0.28	0.02	0.42
Li ₂ O	4.17	4.03	4.25	4.57	4.21	0.15	4.26
MgO	1.76	1.71	1.80	1.97	1.79	0.07	1.72
MnO	1.34	1.30	1.38	1.48	1.36	0.05	1.34
Na ₂ O	16.93	16.45	17.37	16.85*	16.88	0.32	16.80
NiO	0.52	0.51	0.54	0.60	0.53	0.03	0.57
SiO ₂	47.41	50.19	48.57	49.31	48.76	0.82	48.73
TiO ₂	0.66	0.63	0.67	0.72	0.65	0.03	0.70
ZnO	0.37	0.24	0.27	0.26	0.26	0.04	
ZrO ₂	0.44	0.42	0.46	0.48	0.48	0.08	0.46
 OXIDE SUMS	 98.61	 100.31	 100.85	 102.94	 100.41		 100.00
Fe ²⁺ /Fe ³⁺	0.25	0.26	0.22	0.22	0.23	0.01	0.22
 ANION WT%							
Cl	0.063	0.212	0.055	0.059	0.101	0.047	
F	0.005	0.010	0.017	0.010	0.008	0.005	

* this analysis had a significantly higher Na₂O content than the remaining nine samples by ICP analysis and the Na concentration measured by AA was substituted and not bias corrected

Glass Viscosity Analyses

The EA glass viscosity as a function of inverse temperature is given in Figure 1. The Fulcher equation of best fit to the measured data is

$$\log \eta \text{ (poise)} = -1.4913 + 2414.447/(T(^{\circ}\text{C})-235.99) \quad (1)$$

The EA glass viscosity calculated from Equation 1 at the DWPF melt temperature of 1150°C is 14.1 poise. The EA glass viscosity calculated from the DWPF processing algorithms¹⁰ and the Corning Glass Works chemical analysis of the glass is 19.98 poise. The viscosity calculated using the SRS chemical analysis of the EA glass is 19.8 poise.

Figure 1. Fulcher plot of the viscosity of the EA glass.

Glass Homogeneity Analyses

X-ray Diffraction analysis indicated that the glass was x-ray amorphous and contained no crystalline species. During optical microscopy, individual glass grains were determined to be green while others were amber in color. The different colored grain were hand separated and examined by SEM/EDAX. The light element EDAX detector indicated that the green grains appeared to have more carbon than the amber colored grains indicating that the green color was associated with more reduced glass. The green grains were evenly distributed throughout the glass indicating that the bulk redox was homogeneous as confirmed by the chemical analyses in Table 2.

Glass Durability Analyses

Multielement Standard Analysis

During PCT analysis, a multielement solution standard was used by each researcher to ensure that the solution analyses were accurate. Researcher one ran the multielement solution standard before leachate analysis began and after every 5 leachate samples in order to assess any short term bias in the leachate analyses due to instrumental drift (Appendix III). Analysis of the solution standard data indicated that there was less than 0.8 ppm bias in the ICP analyses for Na, Li, Al, Fe, and B, over 5 ppm bias in the ICP analyses for Si, and less than 0.4 ppm bias in the Atomic Absorption (AA) analyses for K. The data also indicated that there was ~0.15 ppm low bias in the Na determinations made by AA compared to the Na determinations by ICP analysis. Similar results were obtained by the other researchers. The instrumental drift was considered insignificant.

Standard Glass Analysis

Historical control charting using PNL's Approved Reference Material (ARM-1) as the standard glass as the PCT standard glass did not indicate any significant bias in the elemental releases (in ppm) for all elements whether the test was performed in Teflon[®] or Parr 304L steel vessels (Table 3). All the standard glass elemental releases used in this study fell within one-sigma of the average elemental release for ARM-1 glass since May, 1989. Hence, no long term bias corrections were made to the EA glass solution data set. Varying dilution factors were used by each researcher but the solution data sets between researchers was in agreement. The ARM-1 measured pH values were slightly lower for researcher 2 (Table 3) as were the EA glass measured pH values.

EA Glass Analysis

The PCT leachate pH and leachate concentrations in ppm measured for the EA glass are given in Table 4. The leachates had to be diluted prior to analysis by ICP or AA in order to match the standardization concentrations of the respective instruments. Varying dilution factors were used by each researcher. The pH values given for researcher 2 were bias corrected on a $1/[H^+]$ linear basis based on the low value measured for the ARM-1 glass.

The leachate concentrations measured for the respective elements in the EA glass by the various researchers are in agreement. The data in the 22 mL 304L Parr Bombs appear somewhat higher than the average leachate concentrations in the Teflon[®] vessels for the same researcher (Table 4). However, these values are within the average leachate concentrations measured by the other researchers in the Teflon[®] vessels. Varying the available head space in the 22 mL steel vessels appears to have no effect on leachate concentrations.

Table 3. PCT Analysis of the ARM-1 Standard Glass

SAMPLE	ADS #	RESEARCHER	NOTEBOOK	PCT VERSION	TYPE OF VESSEL	SIZE OF VESSEL (ML)
ARM-1-7-1	200067152	1	WSRC-NB-91-199	3.0	TEFLON	60
ARM-1-7-2	200067153	1	WSRC-NB-91-199	3.0	TEFLON	60
ARM-1-7-3	200067156	1	WSRC-NB-91-199	3.0	TEFLON	60
ARM-1-7-AVG % STD DEV						
ARM-1-7-1	200068356	2	WSRC-NB-91-200	3.0	TEFLON	60
ARM-1-7-2	200068357	2	WSRC-NB-91-200	3.0	TEFLON	60
ARM-1-7-3	200068358	2	WSRC-NB-91-200	3.0	TEFLON	60
ARM-1-7-AVG % STD DEV						
T-ARM-1-1	200069692	3	DPSTN-4793	3.0	TEFLON	60
T-ARM-1-2	200069693	3	DPSTN-4793	3.0	TEFLON	60
T-ARM-1-3	200069693	3	DPSTN-4793	3.0	TEFLON	60
T-ARM-1-AVG % STD DEV						
SS-ARM-1-1	200069695	3	DPSTN-4793	3.0	PARR STEEL	22
SS-ARM-1-2	200069698	3	DPSTN-4793	3.0	PARR STEEL	22
SS-ARM-1-3	200069699	3	DPSTN-4793	3.0	PARR STEEL	22
SS-ARM-1-AVG % STD DEV						
SS-ARM-1-1	200069701	3	DPSTN-4793	3.0	PARR STEEL	22
SS-ARM-1-2	200069702	3	DPSTN-4793	3.0	PARR STEEL	22
SS-ARM-1-AVG % STD DEV						

Table 3. PCT Analysis of the ARM-1 Standard Glass (Continued)

SAMPLE	mL OF LEACHANT	GMS OF GLASS	MEASURED pH	CONCENTRATIONS (ppm)			
				B	Li	Na*	Si
ARM-1-7-1	40	4.0	10.34	17.71	13.89	38.03	60.47
ARM-1-7-2	40	4.0	10.33	17.97	14.23	38.75	61.45
ARM-1-7-3	40	4.0	10.32	18.03	14.09	38.51	61.13
ARM-1-7-AVG			10.33	17.90	14.07	38.43	61.02
% STD DEV			0.01	0.14	0.14	0.30	0.41
ARM-1-7-1	35	3.5	9.38	18.11	14.31	39.95	60.71
ARM-1-7-2	35	3.5	9.40	18.32	14.45	37.17	60.67
ARM-1-7-3	35	3.5	9.35	17.12	13.46	34.83	57.18
ARM-1-7-AVG			9.38	17.85	14.07	37.32	59.52
% STD DEV			0.02	0.52	0.44	2.09	1.65
T-ARM-1-1	40	4.0	10.28	17.14	14.08	37.51	59.21
T-ARM-1-2	40	4.0	10.38	17.65	14.41	38.23	60.26
T-ARM-1-3	40	4.0	10.29	17.12	14.11	37.52	59.40
T-ARM-1-AVG			10.32	17.31	14.20	37.75	59.62
% STD DEV			0.04	0.25	0.15	0.34	0.45
SS-ARM-1-1	19	1.9	10.38	18.71	15.01	39.84	62.66
SS-ARM-1-2	19	1.9	10.29	17.73	14.39	38.49	60.68
SS-ARM-1-3	19	1.9	10.29	19.50	15.25	40.87	63.38
SS-ARM-1-AVG			10.32	18.65	14.88	39.73	62.24
% STD DEV			0.04	0.72	0.36	0.97	1.14
SS-ARM-1-1	15	1.5	10.34	18.13	14.60	38.78	61.22
SS-ARM-1-2	15	1.5	10.38	19.78	15.65	41.62	64.44
SS-ARM-1-AVG			10.36	18.96	15.13	40.20	62.83
% STD DEV			0.02	0.83	0.52	1.42	1.61

* measured by ICP

Table 4. PCT Analysis of the Environmental Assessment Glass

SAMPLE	ADS #	RESEARCHER	NOTEBOOK	PCT VERSION	TYPE OF VESSEL	SIZE OF VESSEL (ML)
EA-1-7-1	2000267144	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-1-7-2	2000267145	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-1-7-3	2000267148	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-1-AVG % STD DEV						
EA-2-7-1	2000267149	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-2-7-2	2000267150	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-2-7-3	2000267151	1	WSRC-NB-91-199	3.00	TEFLON	60
EA-2-AVG % STD DEV						
EA-7-1	200068359	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-7-2	200068360	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-7-3	200068361	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-7-4	200068362	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-7-5	200068363	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-7-6	200068364	2	WSRC-NB-91-200	3.00	TEFLON	60
EA-AVG % STD DEV						
T-EA-1	200069668	3	DPSTN-4793	3.00	TEFLON	60
T-EA-2	200069671	3	DPSTN-4793	3.00	TEFLON	60
T-EA-3	200069679	3	DPSTN-4793	3.00	TEFLON	60
T-EA-4	200069685	3	DPSTN-4793	3.00	TEFLON	60
EA-T-AVG % STD DEV						
SS-EA-19-1	200069669	3	DPSTN-4793	3.00	PARR STEEL	22
SS-EA-19-2	200069672	3	DPSTN-4793	3.00	PARR STEEL	22
SS-EA-19-3	200069677	3	DPSTN-4793	3.00	PARR STEEL	22
SS-EA-19-4	200069681	3	DPSTN-4793	3.00	PARR STEEL	22
EA-SS-19-AVG % STD DEV						
EA-SS-15-1	200069670	3	DPSTN-4793	3.00	PARR STEEL	22
EA-SS-15-2	200069673	3	DPSTN-4793	3.00	PARR STEEL	22
EA-SS-15-3	200069676	3	DPSTN-4793	3.00	PARR STEEL	22
EA-SS-15-4	200069686	3	DPSTN-4793	3.00	PARR STEEL	22
EA-SS-A5-AVG % STD DEV						

Table 4. PCT Analysis of the Environmental Assessment Glass (Continued).

SAMPLE	mL OF LEACHANT	GMS OF GLASS	MEASURED pH	CONCENTRATIONS (ppm)			
				B	Li	Na*	Si
EA-1-7-1	40	4.00	11.80	567.96	210.71	1738.35	1048.41
EA-1-7-2	40	4.00	11.79	593.57	211.19	1819.70	1061.93
EA-1-7-3	40	4.00	11.80	605.97	212.86	1857.20	1070.91
EA-1-AVG			11.80	589.17	211.59	1805.08	1060.42
% STD DEV			0.00	15.83	0.92	49.61	9.25
EA-2-7-1	40	4.00	11.86	468.52	163.27	1380.80	780.29
EA-2-7-2	40	4.00	11.88	610.00	225.05	1854.87	1128.56
EA-2-7-3	40	4.00	11.88	523.05	171.77	1542.60	832.21
EA-2-AVG			11.87	533.86	186.70	1592.76	913.69
% STD DEV			0.01	58.26	27.34	196.76	153.41
EA-7-1	35	3.50	12.01**	609.42	192.06	1685.50	908.43
EA-7-2	35	3.50	12.01	615.07	187.92	1724.34	909.33
EA-7-3	35	3.50	12.01	634.81	195.74	1770.69	938.30
EA-7-4	35	3.50	12.01	638.54	204.01	1771.35	956.44
EA-7-5	35	3.50	12.01	649.05	208.11	1789.02	965.06
EA-7-6	35	3.50	12.01	584.70	186.73	1644.01	892.60
EA-AVG			12.01	621.93	195.76	1730.82	928.36
% STD DEV			0.00	21.47	7.93	52.04	26.68
T-EA-1	40	4.00	11.88	499.85	162.08	1429.74	763.41
T-EA-2	40	4.00	11.88	493.34	161.27	1408.62	746.67
T-EA-3	40	4.00	11.89	517.52	167.81	1480.44	782.22
T-EA-4	40	4.00	11.89	560.09	183.35	1572.63	825.27
EA-T-AVG			11.89	517.70	168.63	1472.86	779.39
% STD DEV			0.00	26.02	8.87	63.24	29.32
SS-EA-19-1	19	1.90	11.92	577.41	180.78	1633.95	798.81
SS-EA-19-2	19	1.90	11.90	566.13	177.48	1604.19	791.43
SS-EA-19-3	19	1.90	11.95	576.06	180.48	1635.24	794.04
SS-EA-19-4	19	1.90	11.91	584.31	183.60	1650.21	803.25
EA-SS-19-AVG			11.92	575.98	180.59	1630.90	796.88
% STD DEV			0.02	6.49	2.17	16.69	4.53
EA-SS-15-1	15	1.50	11.98	596.10	190.26	1670.40	846.96
EA-SS-15-2	15	1.50	11.92	601.41	191.52	1692.06	852.09
EA-SS-15-3	15	1.50	11.93	587.04	196.68	1640.88	848.55
EA-SS-15-4	15	1.50	11.95	572.67	193.11	1606.35	830.64
EA-SS-A5-AVG			11.95	589.31	192.89	1652.42	844.56
% STD DEV			0.02	10.89	2.41	32.21	8.25

* measured by ICP

** bias corrected based on ARM-1 pH measurements

Table 5. PCT Analysis of the Environmental Assessment Glass.

SAMPLE	NORMALIZED MASS LOSS				LOG NORMALIZED MASS LOSS				ΔG_{hyd} (Kcal/ mole)*
	(g/L)				(g/L)				
	B	Li	Na	Si	B	Li	Na	Si	
EA-1-7-1	16.18	10.64	13.95	4.60	1.21	1.03	1.14	0.66	-13.68
EA-1-7-2	16.91	10.67	14.60	4.66	1.23	1.03	1.16	0.67	-13.65
EA-1-7-3	17.26	10.75	14.91	4.70	1.24	1.03	1.17	0.67	-13.68
EA-1-AVG	16.79	10.69	14.49	4.66	1.22	1.03	1.16	0.67	-13.67
% STD DEV	0.45	0.05	0.40	0.04	0.01	0.00	0.01	0.00	
EA-2-7-1	13.35	8.25	11.08	3.43	1.13	0.92	1.04	0.53	-13.89
EA-2-7-2	17.38	11.37	14.89	4.95	1.24	1.06	1.17	0.69	-13.96
EA-2-7-3	14.90	8.68	12.38	3.65	1.17	0.94	1.09	0.56	-13.96
EA-2-AVG	15.21	9.43	12.78	4.01	1.18	0.97	1.10	0.60	-13.93
% STD DEV	1.66	1.38	1.58	0.67	0.05	0.06	0.05	0.07	
EA-7-1	17.36	9.70	13.53	3.99	1.24	0.99	1.13	0.60	-14.42
EA-7-2	17.52	9.49	13.84	3.99	1.24	0.98	1.14	0.60	-14.42
EA-7-3	18.09	9.89	14.21	4.12	1.26	1.00	1.15	0.61	-14.42
EA-7-4	18.19	10.30	14.22	4.20	1.26	1.01	1.15	0.62	-14.42
EA-7-5	18.49	10.51	14.36	4.24	1.27	1.02	1.16	0.63	-14.42
EA-7-6	16.66	9.43	13.19	3.92	1.22	0.97	1.12	0.59	-14.42
EA-AVG	17.72	9.89	13.89	4.08	1.25	0.99	1.14	0.61	-14.42
% STD DEV	0.61	0.40	0.42	0.12	0.02	0.02	0.01	0.01	
T-EA-1	14.24	8.19	11.47	3.35	1.15	0.91	1.06	0.53	-13.96
T-EA-2	14.06	8.14	11.31	3.28	1.15	0.91	1.05	0.52	-13.96
T-EA-3	14.74	8.48	11.88	3.43	1.17	0.93	1.07	0.54	-13.99
T-EA-4	15.96	9.26	12.62	3.62	1.20	0.97	1.10	0.56	-13.99
EA-T-AVG	14.75	8.52	11.82	3.42	1.17	0.93	1.07	0.53	-13.97
% STD DEV	0.74	0.45	0.51	0.13	0.02	0.02	0.02	0.02	
SS-EA-19-1	16.45	9.13	13.11	3.51	1.22	0.96	1.12	0.54	-14.10
SS-EA-19-2	16.13	8.96	12.87	3.47	1.21	0.95	1.11	0.54	-14.03
SS-EA-19-3	16.41	9.12	13.12	3.49	1.22	0.96	1.12	0.54	-14.20
SS-EA-19-4	16.65	9.27	13.24	3.53	1.22	0.97	1.12	0.55	-14.06
EA-SS-19-AVG	16.41	9.12	13.09	3.50	1.22	0.96	1.12	0.54	-14.10
% STD DEV	0.18	0.11	0.13	0.02	0.00	0.01	0.00	0.00	
EA-SS-15-1	16.98	9.61	13.41	3.72	1.23	0.98	1.13	0.57	-14.31
EA-SS-15-2	17.13	9.67	13.58	3.74	1.23	0.99	1.13	0.57	-14.10
EA-SS-15-3	16.72	9.93	13.17	3.72	1.22	1.00	1.12	0.57	-14.13
EA-SS-15-4	16.32	9.75	12.89	3.65	1.21	0.99	1.11	0.56	-14.20
EA-SS-A5-AVG	16.79	9.74	13.26	3.71	1.22	0.99	1.12	0.57	-14.19
% STD DEV	0.31	0.12	0.26	0.04	0.01	0.01	0.01	0.00	

* ΔG_{hyd} without pH correction is -7.28 Kcal/mole based on CGW analysis in Table 2

The leachate concentrations are reported as normalized elemental losses, NC_i , released from the glass in grams of glass per L of leachant. This has the advantage that the release concentrations in parts per million are normalized by the weight fraction of that element present in the glass. The normalized release, NC_i , is a function of (1) the mass fraction of that element in the glass, (2) the exposed surface area of the glass, and (3) the leachate volume. Since the latter two are held constant, the normalized release is expressed as:

$$NC_i = \frac{C_i}{F_i} \quad (1)$$

where NC_i = normalized release ($g_{\text{glass}}/L_{\text{leachant}}$)
 C_i = mass of element "i" in the solution (g_i/m^3)
 F_i = fraction of element "i" in the glass (g_i/g_{glass})

The units of NC_i are normally expressed as grams of glass dissolved per liter of leachant. The normalized releases were calculated using the Corning analyzed glass composition given in Table 2. The normalized releases were calculated in grams of glass based on B, Li, Si, Na, and K leached per liter of leachate (g/L) as given in Equation 1. The calculation of NC_i and $\log NC_i$ are given in Table 5.

CONCLUSIONS

The chemical analysis of the EA glass indicates that the glass is within the target composition specified and has an Fe^{2+}/Fe^{3+} ratio of 0.23 compared to Corning Glass Works' value of 0.22. The chemical analyses in this study verify the Corning Glass Works analysis except for the lower concentration of La_2O_3 measured in this study. In addition, minor amounts of ZnO, Cl and F were detected in the glass. The presence of trace amounts of anions is not considered significant because the analytic determinations were so close to the detection limits of the measurement technique.

The chemical composition of the 1000 pounds of glass was determined to be homogeneous. The glass was x-ray amorphous and found to be composed of individual grains which varied in redox but were homogeneously distributed. The PCT leachate data of the EA glass appears to be internally consistent. No significant long term or short term instrumental analytic bias was observed. The leachate results were comparable in Teflon[®] and in Parr 304L stainless steel vessels with a smooth internal finish. The EA glass fabricated by Corning Glass Works is suitable as a composition, redox, and durability Standard Reference Material.

ACKNOWLEDGEMENT

The authors would like to acknowledge the efforts of C.J. Coleman of SRTC in verifying the EA glass composition.

This page intentionally left blank.

REFERENCES

1. **Waste Acceptance Preliminary Specifications for the Defense Waste Processing Facility High-Level Waste Form**, U. S. Department of Energy, Office of Civilian Radioactive Waste Management, USDOE Document OGR/B-8, Washington, DC (1988).
2. C. M. Jantzen and N. E. Bibler, **"Product Consistency Test (PCT) and Test Protocol,"** USDOE Report DPST-87-575, E.I duPont deNemours & Co, Savannah River Laboratory, Aiken, SC (1987).
3. C. M. Jantzen and N. E. Bibler, **"Nuclear Waste Product Consistency Test (PCT) -Version 3.0,"** USDOE Report WSRC-TR-90-539, Rev. 1, Westinghouse Savannah River Co., Savannah River Laboratory, Aiken, SC (November, 1990).
4. N.E. Bibler and C.M. Jantzen, **"The Product Consistency Test and Its Role in the Waste Acceptance Process for DWPF Glass,"** Waste Management '89, Volume I, R.G. Post and M.E. Wacks (Eds.), University of Arizona, 743-749 (1989).
5. C.M. Jantzen and N.E. Bibler, **"The Product Consistency Test for the DWPF Wasteform,"** Requirements for Waste Acceptance and Quality Control, Proceedings of the 2nd International Seminar on Radioactive Waste Products, E. Warnecke, R. Odoj, and R. Simon (Eds.), Kernforschungsanlage (KFA) Research Center, Julich, Federal Republic of Germany, 609-622 (1990).
6. G. F. Piepel, T. E. Jones, D. L. Eggett, G. B. Mellinger, **"Product Consistency Test Round Robin Conducted by the Materials Characterization Center - Summary Report,"** USDOE Report PNL-6967, Materials Characterization Center, Battelle Pacific Northwest Laboratories, Richland, WA (1989).
7. N. E. Bibler and J. K. Bates, **"Product Consistency Leach Tests of Savannah River Site Radioactive Waste Glasses,"** Scientific Basis for Nuclear Waste Management, XIII, V. M. Oversby and P. W. Brown (Eds.), Materials Research Society, Pittsburgh, PA, 327-338 (1990).
8. U.S. Department of Energy, **"Environmental Assessment Waste Form Selection for SRP High-Level Waste,"** U.S. DOE Report DOE-EA-0179 (July, 1982).
9. C.M. Jantzen, **"Relationship of Glass Composition to Glass Viscosity, Resistivity, Liquidus Temperature, and Durability: First Principles Process-Product Models for Vitrification of Nuclear Waste,"** Proceedings of the 5th International Symposium on Ceramics in Nuclear Waste Management, G.G. Wicks, D.F. Bickford, and R. Burnell (Eds.), American Ceramic Society, Westerville, OH, 37-51 (1991).
10. M. J. Plodinec, **"Factors Affecting the Iron Oxidation State and Foaming in SRP Waste Glass,"** Proceedings of the Symposium on High Temperature Materials Chemistry, D. D. Cubicciotti and D. L. Hildebrand (Eds.), The Electrochemical Society, Pennington, New Jersey, 201-209 (1982).

11. C. M. Jantzen, D. F. Bickford and D. G. Karraker, "Time-Temperature-Transformation Kinetics in SRL Waste Glass," Advances in Ceramics, V. 8 G. G. Wicks and W. A. Ross (Eds.), 30-38 (1984).
12. D. F. Bickford and R. B. Diemer, Jr., "Redox Control of Electric Melters with Complex Feed Compositions, Part I. Analytical Methods and Models," J. Non-Cryst. Solids, 84, 276-284 (1986).
13. D. F. Bickford and R. B. Diemer, Jr., D. C. Iverson "Redox Control of Electric Melters with Complex Feed Compositions, Part II. Preliminary Limits for Radioactive Waste Melters," J. Non-Cryst. Solids, 84, 285-291 (1986).
14. D. F. Bickford, R. C. Probst, and M. J. Plodinec, "Control of Radioactive Waste Glass Melters: Part III. Glass Electrical Stability," Advances in the Fusion of Glass, D. F. Bickford, et. al. (Eds.), The American Ceramic Society, Westerville, OH, 19.1-19.17 (1988).
15. L. R. Bunnell, "Laboratory Work in Support of West Valley Glass Development," USDOE Report PNL-6539, Battelle Pacific Northwest Laboratory, Richland, WA, (May, 1988).
16. C.M. Jantzen and M.J. Plodinec, "Composition and Redox Control of Waste Glasses: Recommendation for Process Control Limit," USDOE Report DPST-86-773, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (November, 1986).
17. C.M. Jantzen, "Verification and Standardization of Glass Redox Measurement for DWPF," USDOE Report DPST-89-222, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (January, 1989).
18. G.F. Piepel and G.B. Mellinger, "Statistical Aspects of Compliance with the WAPS Radionuclide Release Specification," Proceedings of the 4th International Symposium on Ceramics in Nuclear Waste Management, III, G.B. Mellinger (Ed.), Ceramic Transactions, V. 9, American Ceramic Society, Westerville, OH, 483-494 (1990).
19. C.M. Jantzen, "Verification of Glass Composition and Strategy for SGM and DWPF Glass Composition Determination," USDOE Report DPST-86-708, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (March 30, 1987).
20. C.M. Jantzen, "Composition of Linde IE95 (AW500) Zeolite Fraction of Sludge," USDOE Report DPST-88-623, E.I. duPont deNemours & Co., Savannah River Laboratory, Aiken, SC (June, 1988).
21. E.W. Baumann, "Colorimetric Determination of Iron (II) and Iron (III) in Glass," Analyst, v. 117, 913-916 (1992).
22. Waste Form Compliance Plan for the Defense Waste Processing Facility, Revision 0, USDOE Document WSRC-SW4-6, Westinghouse Savannah River Company, Aiken, SC, March 1990.

23. T.A. Policke, **"Demonstration of Method DPST-88-272, Sodium Peroxide Fusion Dissolution of Sludge, Glass, and Melter Feed for Elemental Analysis,"** USDOE Report WSRC-TR-92-313, Westinghouse Savannah River Company, Aiken, SC (June, 1992).

This page intentionally left blank.

APPENDIX I Corning Glass Works Chemical Analysis of EA Glass

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Sample 1

	Dissolution 1		Dissolution 2		Dissolution 3	
	Read 1	Read 2	Read 1	Read 2	Read 1	Read 2
Al ₂ O ₃	3.75	3.72	3.72	3.72	3.69	3.69
B ₂ O ₃	11.1	11.2	11.2	11.2	11.3	11.4
CaO	1.12	1.12	1.12	1.12	1.11	1.11
Fe ₂ O ₃	7.39	7.38	7.52	7.52	7.36	7.31
FeO	1.45	1.46	1.36	1.36	1.47	1.48
K ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
La ₂ O ₃	0.42	0.42	0.42	0.42	0.42	0.42
Li ₂ O	4.28	4.29	4.25	4.24	4.26	4.26
MgO	1.74	1.72	1.72	1.72	1.72	1.71
MnO	1.35	1.34	1.35	1.35	1.35	1.34
Na ₂ O	16.8	16.8	16.8	16.8	16.8	16.8
NiO	0.58	0.57	0.57	0.57	0.57	0.57
SiO ₂	49.3	48.9	49.0	49.0	48.6	48.5
TiO ₂	0.71	0.70	0.70	0.70	0.70	0.69
ZrO ₂	0.46	0.46	0.48	0.47	0.46	0.46
Total	100.49	100.12	100.25	100.23	99.85	99.78
Fe ₂ O ₃ (TOT)	9.01	9.01	9.04	9.04	9.00	8.96
Fe(TOT)	6.30	6.30	6.32	6.32	6.29	6.26
FeO	1.45	1.46	1.36	1.36	1.47	1.48
Fe(+2)	1.13	1.13	1.06	1.06	1.14	1.15
Fe(+3)	5.17	5.16	5.26	5.26	5.15	5.11
Fe ₂ O ₃ (+3)	7.39	7.38	7.52	7.52	7.36	7.31
Fe+2/Fe+3	0.22	0.22	0.20	0.20	0.22	0.22

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Sample 2

	Dissolution 1		Dissolution 2		Dissolution 3	
	Read 1	Read 2	Read 1	Read 2	Read 1	Read 2
Al ₂ O ₃	3.67	3.73	3.72	3.69	3.69	3.70
B ₂ O ₃	11.2	11.3	11.2	11.3	11.4	11.3
CaO	1.11	1.12	1.12	1.11	1.12	1.12
Fe ₂ O ₃	7.27	7.35	7.39	7.36	7.40	7.40
FeO	1.47	1.48	1.48	1.50	1.48	1.49
K ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
La ₂ O ₃	0.42	0.42	0.42	0.42	0.41	0.42
Li ₂ O	4.27	4.28	4.26	4.25	4.27	4.24
MgO	1.71	1.71	1.71	1.71	1.72	1.72
MnO	1.33	1.32	1.34	1.33	1.35	1.35
Na ₂ O	16.8	16.8	16.8	16.8	16.8	16.8
NiO	0.56	0.56	0.57	0.57	0.57	0.57
SiO ₂	48.7	48.8	48.8	48.5	48.7	48.8
TiO ₂	0.69	0.70	0.70	0.70	0.70	0.70
ZrO ₂	0.47	0.47	0.48	0.47	0.46	0.47
Total	99.71	100.08	100.03	99.75	100.11	100.12
Fe ₂ O ₃ (TOT)	8.91	9.00	9.04	9.03	9.05	9.06
FeO (TOT)	6.23	6.29	6.32	6.31	6.33	6.33
FeO	1.47	1.48	1.48	1.50	1.48	1.49
Fe(+2)	1.14	1.15	1.15	1.17	1.15	1.16
Fe(+3)	5.09	5.14	5.17	5.15	5.18	5.18
Fe ₂ O ₃ (+3)	7.27	7.35	7.39	7.36	7.40	7.40
Fe+2/Fe+3	0.22	0.22	0.22	0.23	0.22	0.22

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Sample 3

	Dissolution 1		Dissolution 2		Dissolution 3	
	Read 1	Read 2	Read 1	Read 2	Read 1	Read 2
Al2O3	3.66	3.70	3.68	3.72	3.73	3.71
B2O3	11.3	11.3	11.2	11.3	11.4	11.4
CaO	1.10	1.12	1.11	1.12	1.12	1.12
Fe2O3	7.21	7.27	7.44	7.50	7.43	7.41
FeO	1.47	1.47	1.38	1.38	1.43	1.43
K2O	0.04	0.04	0.04	0.04	0.04	0.04
La2O3	0.42	0.42	0.41	0.41	0.42	0.42
Li2O	4.27	4.28	4.25	4.25	4.27	4.25
MgO	1.69	1.70	1.71	1.72	1.73	1.72
MnO	1.32	1.33	1.34	1.35	1.35	1.35
Na2O	16.8	16.8	16.9	16.9	16.8	16.7
NiO	0.56	0.57	0.57	0.57	0.57	0.57
SiO2	48.0	48.3	48.6	48.9	49.3	49.1
TiO2	0.69	0.69	0.69	0.70	0.70	0.70
ZrO2	0.44	0.45	0.45	0.45	0.44	0.44
Total	98.97	99.44	99.77	100.31	100.73	100.36
Fe2O3(TOT)	8.85	8.91	8.98	9.04	9.02	9.00
Fe(TOT)	6.19	6.23	6.28	6.32	6.30	6.29
FeO	1.47	1.47	1.38	1.38	1.43	1.43
Fe(+2)	1.14	1.14	1.07	1.07	1.11	1.11
Fe(+3)	5.04	5.09	5.20	5.25	5.19	5.18
Fe2O3(+3)	7.21	7.27	7.44	7.50	7.43	7.41
Fe+2/Fe+3	0.23	0.22	0.21	0.20	0.21	0.21

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Sample 4

	Dissolution 1		Dissolution 2		Dissolution 3	
	Read 1	Read 2	Read 1	Read 2	Read 1	Read 2
Al ₂ O ₃	3.67	3.67	3.75	3.72	3.68	3.69
B ₂ O ₃	11.1	11.1	11.3	11.2	11.4	11.4
CaO	1.11	1.11	1.13	1.12	1.11	1.12
Fe ₂ O ₃	7.33	7.34	7.49	7.45	7.39	7.41
FeO	1.42	1.43	1.42	1.41	1.40	1.40
K ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
La ₂ O ₃	0.41	0.41	0.42	0.42	0.41	0.41
Li ₂ O	4.28	4.28	4.26	4.26	4.26	4.26
MgO	1.70	1.70	1.73	1.72	1.71	1.72
MnO	1.33	1.33	1.35	1.35	1.35	1.35
Na ₂ O	16.8	16.9	16.8	16.9	16.8	16.7
NiO	0.56	0.56	0.57	0.57	0.57	0.57
SiO ₂	48.2	48.5	49.1	48.8	48.6	48.8
TiO ₂	0.69	0.69	0.70	0.70	0.69	0.69
ZrO ₂	0.45	0.45	0.47	0.47	0.45	0.45
Total	99.09	99.51	100.53	100.13	99.86	100.01
Fe ₂ O ₃ (TOT)	8.91	8.93	9.07	9.02	8.95	8.97
Fe (TOT)	6.23	6.24	6.34	6.30	6.26	6.27
FeO	1.42	1.43	1.42	1.41	1.40	1.40
Fe(+2)	1.10	1.11	1.10	1.10	1.09	1.09
Fe(+3)	5.12	5.13	5.24	5.21	5.17	5.18
Fe ₂ O ₃ (+3)	7.33	7.34	7.49	7.45	7.39	7.41
Fe+2/Fe+3	0.22	0.22	0.21	0.21	0.21	0.21

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Sample 5

	Dissolution 1		Dissolution 2		Dissolution 3	
	Read 1	Read 2	Read 1	Read 2	Read 1	Read 2
Al ₂ O ₃	3.70	3.68	3.70	3.72	3.69	3.69
B ₂ O ₃	11.3	11.3	11.2	11.2	11.4	11.4
CaO	1.11	1.11	1.12	1.13	1.12	1.12
Fe ₂ O ₃	7.31	7.29	7.35	7.41	7.38	7.35
FeO	1.48	1.49	1.48	1.49	1.46	1.45
K ₂ O	0.04	0.04	0.04	0.04	0.04	0.04
La ₂ O ₃	0.42	0.41	0.41	0.42	0.41	0.41
Li ₂ O	4.28	4.29	4.28	4.25	4.23	4.26
MgO	1.71	1.70	1.71	1.73	1.73	1.72
MnO	1.33	1.33	1.34	1.35	1.35	1.35
Na ₂ O	16.8	16.9	16.9	16.9	16.7	16.7
NiO	0.56	0.57	0.57	0.58	0.57	0.57
SiO ₂	48.5	48.4	48.6	49.0	48.9	48.7
TiO ₂	0.69	0.69	0.70	0.70	0.69	0.69
ZrO ₂	0.47	0.47	0.48	0.48	0.46	0.46
Total	99.70	99.67	99.88	100.40	100.13	99.91
Fe ₂ O ₃ (TOT)	8.96	8.95	9.00	9.07	9.01	8.97
Fe(TOT)	6.26	6.26	6.29	6.34	6.30	6.27
FeO	1.48	1.49	1.48	1.49	1.46	1.45
Fe(+2)	1.15	1.16	1.15	1.16	1.13	1.13
Fe(+3)	5.11	5.10	5.14	5.18	5.16	5.14
Fe ₂ O ₃ (+3)	7.31	7.29	7.35	7.41	7.38	7.35
Fe+2/Fe+3	0.22	0.23	0.22	0.22	0.22	0.22

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-036

Exhibit A: Quantitative Chemical Analysis

Sample Description: 1000 lb. Standard

Summary

	Target	+/-	Mean	Dif	Std Dev	RSD (%)
Al2O3	3.67	0.18	3.70	0.03	0.023	0.6
B2O3	11.1	0.56	11.3	0.2	0.097	0.9
CaO	1.13	0.06	1.12	-0.01	0.007	0.6
Fe2O3	8.08	0.40	7.38	-0.70	0.074	1.0
FeO	0.89		1.45		0.041	2.9
K2O	0.04	0.004	0.04	0.00	0.000	0.0
La2O3	0.41	0.04	0.42	0.01	0.005	1.2
Li2O	4.28	0.21	4.26	-0.02	0.015	0.4
MgO	1.66	0.08	1.72	0.06	0.011	0.6
MnO	1.34	0.07	1.34	0.00	0.010	0.8
Na2O	16.7	0.84	16.8	0.10	0.061	0.4
NiO	0.61	0.06	0.57	-0.04	0.005	0.9
SiO2	48.95	4.49	48.73	-0.22	0.302	0.6
TiO2	0.71	0.07	0.70	-0.01	0.006	0.8
ZrO2	0.41	0.04	0.46	0.05	0.012	2.7
Total	99.99		99.96			
Redox	.1-.3		.22			

*2Fe as
Fe2O3*

9.07

8.99

APPENDIX II Savannah River Technology Center Chemical Analysis of EA Glass

(SPREADSHEET REVISION 8.0, OCTOBER 23, 1990)													
GLASS ID= 1-TOP-A													
FACTORS FOR													
ANALYTIC	ELEMENT	GRAV	OXIDE	BIAS	W.T.	NORM	M.W.	FRACTION	NORM	MOLE %	COMPONENT	FREE	NEO
TECHNIQUE	WT%	FACTOR	WT%	CORRECTION	OXIDE	WT%			OXIDE	FREE	FREE	HYDRATION	KCAL/KG
Al2O3	1.798	1.8995	3.3973	1.05	3.5788	3.4511	101.9600	0.0351	2.1946	3.0400	0.0867	-0.0439	1.0673
CaO	0.856	1.3992	1.1977	1.00	1.1977	1.2167	56.0784	0.0214	1.3350	16.1160	-0.2151	0.0287	-3.4420
Fe2O3	6.462	1.4297	7.4667	1.00	7.4667	7.5668	159.6922	0.0468	2.9233	15.5000	0.4531	-0.0585	7.2492
FeO	N/A	1.2865	1.5928	1.00	1.5928	1.6180	71.8464	0.0222	1.3857	14.6090	-0.2024	0.0277	-3.2387
MgO	1.070	1.6583	1.7744	1.00	1.7744	1.8025	40.3114	0.0440	2.7513	13.8880	-0.3921	0.0550	-6.1131
MnO	1.049	1.2912	1.3545	1.00	1.3545	1.3759	70.9374	0.0191	1.1835	14.8710	-0.1775	0.0239	-2.8394
Na2O	11.990	1.3480	16.1625	1.04	16.8614	16.4184	61.9780	0.2720	17.0047	28.8150	-4.8999	0.3401	-78.3911
Li2O	1.947	2.1525	4.1908	1.00	4.1908	4.2573	29.8774	0.1403	6.7677	22.7400	-1.9938	0.1754	-31.8975
NO	0.412	1.2726	0.5243	1.00	0.5243	0.5328	74.7084	0.0070	0.4367	14.3470	-0.0629	0.0088	-1.0089
SiO2	22.425	2.1393	47.9738	1.02	49.0271	48.7333	60.0848	0.8160	51.0026	5.5900	0.9871	0.0000	15.7928
Cr2O3	0.000	1.4618	0.0000	1.00	0.0000	0.0000	151.9974	0.0000	0.0000	37.9000	0.0000	0.0000	0.0000
B2O3	3.453	3.2201	11.1190	1.00	11.1190	11.2950	69.6204	0.1597	9.8827	9.9300	-0.9913	0.0000	-15.8591
UO2		1.1344	0.0000	1.00	0.0000	0.0000	270.0388	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000	1.00	0.0000	0.0000	284.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	0.000	1.1826	0.0000	1.00	0.0000	0.0000	103.6194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZrO2	0.359	1.3508	0.4849	1.00	0.4849	0.4928	123.2188	0.0038	0.2480	45.1000	0.1109	0.0098	1.7749
TiO2	0.385	1.6680	0.6422	1.00	0.6422	0.6523	79.8988	0.0080	0.5024	15.9800	0.0803	0.0201	1.2852
P2O5	0.035	1.2046	0.0420	1.00	0.0420	0.0427	94.2034	0.0004	0.0278	-41.7350	-0.0116	0.0006	-0.1863
CaO	0.000	1.0602	0.0000	1.00	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Si2O3	1.1970	1.1970	0.0000	1.00	0.0000	0.0000	291.4982	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
P2O5	0.000	2.2910	0.0000	1.00	0.0000	0.0000	141.9370	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Na2O3	1.1680	1.1680	0.0000	1.00	0.0000	0.0000	336.4782	0.0000	0.0000	-31.1400	-0.0158	0.0015	-0.2533
Y2O3	0.226	1.1728	0.2651	1.00	0.2651	0.2692	325.8100	0.0008	0.0508	-12.9500	0.0000	0.0000	0.0000
BaO	0.000	1.1185	0.0000	1.00	0.0000	0.0000	225.8082	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
PbO	0.000	1.0772	0.0000	1.00	0.0000	0.0000	153.3394	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2	1.2284	1.2284	0.0000	1.00	0.0000	0.0000	223.1900	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
Na2O3	0.000	1.5003	0.0000	1.00	0.0000	0.0000	172.1200	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.202	1.2447	0.2514	1.00	0.2514	0.2554	143.9382	0.0000	0.0031	-2.4000	-0.0046	0.0039	-0.0741
CaO	0.000	1.2518	0.0000	1.00	0.0000	0.0000	81.3900	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0.237						78.5454						
SUMS	52.669		98.4415		100.3781	100.0000		1.5998	100.0000		SUM + pH SI	-7.2589	-116.1320
ALK/SiO2 =	0.506					TEST=					SUM + pH B	-7.2589	
ALK+ B2O3/SiO2 =	0.702					TIME=					pH =		
B2O3/SiO2 =	0.186					SA/V =							
VISCOSITY @TEMP(°C)	20.545												
LIQUIDUS RATIO =	0.055												
LIQUIDUS (°C) =	926												
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FeO3 (OCTOBER 23, 1990)													

(SPREADSHEET REVISION 8.0, OCTOBER 23, 1990)

GLASS ID= 2-TOP-A

FACTORS FOR

	ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	BIAS CORRECTION	BIAS CORRECT OXIDE WT%	NORM OXIDE WT%	MW.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	NEO	KCAL/KG
Al2O3	Na2O2 DISS/ICP	1.844	1.8995	3.4842	1.05	3.6714	3.5137	101.9600	0.0360	2.2346	3.0400	0.0678	-0.0447	1.0947
CaO	MW DISS/ICP	0.872	1.3992	1.2201	1.00	1.2201	1.2304	56.0794	0.0218	1.3502	-16.1160	-0.2176	0.0270	-3.5063
Fe2O3	MW DISS/ICP	6.457	1.4297	7.4871	1.00	7.4871	7.5504	159.6922	0.0469	2.9095	15.5000	0.4510	-0.0562	7.2871
FeO	REDX	N/A	1.2865	1.5698	1.00	1.5698	1.5830	71.8464	0.0218	1.3559	-14.6090	-0.1981	0.0271	-3.1919
MgO	MW DISS/ICP	1.078	1.8593	1.7876	1.00	1.7876	1.8028	40.3114	0.0443	2.7520	-13.8880	-0.3822	0.0550	-8.1586
MnO	MW DISS/ICP	1.060	1.2912	1.3697	1.00	1.3697	1.3802	70.9374	0.0193	1.1973	-14.8710	-0.1781	0.0239	-2.8632
Na2O	MW DISS/ICP	12.109	1.3480	16.3229	1.04	17.0287	16.4610	61.9790	0.2747	17.0502	-28.8150	-4.9130	0.3410	-78.1691
Li2O	MW DISS/ICP	1.970	2.1525	4.2404	1.00	4.2404	4.2783	29.8774	0.1419	8.8076	-22.7400	-2.0029	0.1762	-32.2743
NaO	MW DISS/ICP	0.410	1.2726	0.5218	1.00	0.5218	0.5262	74.7094	0.0070	0.4334	-14.3470	-0.0622	0.0087	-1.0020
SiO2	Na2O2 DISS/ICP	22.497	2.1393	48.1278	1.02	49.1845	48.5348	60.0848	0.8186	50.7992	5.5900	0.9722	0.0000	15.8686
Cr2O3	MW DISS/ICP	0.000	1.4616	0.0000	1.00	0.0000	0.0000	151.9974	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	Na2O2 DISS/ICP	3.518	3.2201	11.3219	1.00	11.3219	11.4178	69.6204	0.1625	10.0919	-9.9300	-1.0021	0.0000	-16.1485
Li2O			1.1344	0.0000	1.00	0.0000	0.0000	270.0388	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000
ThO2			1.1376	0.0000		0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SiO	MW DISS/ICP	0.000	1.1826	0.0000		0.0000	0.0000	103.8194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZrO2	MW DISS/ICP	0.354	1.3508	0.4782	1.00	0.4782	0.4822	123.2188	0.0039	0.2408	45.1000	0.1086	0.0096	1.7502
TiO2	MW DISS/ICP	0.389	1.6690	0.6489	1.00	0.6489	0.6543	79.8988	0.0091	0.5040	15.9900	0.0806	0.0202	1.2885
K2O	MW DISS/AA	0.047	1.2046	0.0561	1.00	0.0561	0.0568	94.2034	0.0006	0.0370	-41.7350	-0.0154	0.0007	-0.2487
CaO	MW DISS/AA	0.004	1.0602	0.0043	1.00	0.0043	0.0044	281.8094	0.0000	0.0010	-46.8200	-0.0004	0.0000	-0.0072
SiO2O3			1.1970	0.0000		0.0000	0.0000	291.4992	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	MW DISS/ICP	0.000	2.2910	0.0000	1.00	0.0000	0.0000	141.9370	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3			1.1680	0.0000		0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Li2O3	MW DISS/ICP	0.242	1.1728	0.2838	1.00	0.2838	0.2862	325.8100	0.0009	0.0541	-31.1400	-0.0168	0.0016	-0.2713
Y2O3			1.2699	0.0000		0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
B2O	MW DISS/ICP	0.000	1.1165	0.0000	1.00	0.0000	0.0000	153.3394	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
PbO	MW DISS/ICP	0.000	1.0772	0.0000		0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2			1.2284	0.0000		0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MgO3	MW DISS/ICP	0.000	1.5003	0.0000	1.00	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	MW DISS/ICP	0.191	1.2447	0.2377	1.00	0.2377	0.2397	81.3800	0.0029	0.1813	-2.4000	-0.0044	0.0036	-0.0701
CaO	MW DISS/ICP	0.000	1.2518	0.0000	1.00	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+Fe3+		0.233												

SLAS	53.040	98.1814	101.1110	100.0000	1.8114	100.0000	SUM + pH Si	-7.3128	0.5918	-117.8400
ALK/SiO2 =	0.510						SUM + pH B	-7.3128		
ALK+ B2O3/SiO2 =	0.708						pH =			
B2O3/SiO2 =	0.199									
VISCOSITY @TEMP(°C)	16.913									
LIQUIDUS RATIO =	0.055									
LIQUIDUS (°C) =	926									

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

GLASS ID# 3-TOP-A

FACTORS FOR

ANALYTIC	ELEMENT	GRAV	OXIDE	BIAS HAS CORRECT	NORM OXIDE	MW	FRACTION	MOLE %	COMPONENT	FREE ENERGY	HYDRATION	NBO	KCAL/KG
TECHNIQUE	WT%	FACTOR	WT%	CORRECTION	OXIDE WT%	WT%			FREE ENERGY				
Al2O3	1.892	1.8895	3.5749	1.05	3.7670	3.6174	0.0369	2.3007	3.0400	0.0699	0.0699	-0.0460	1.1231
CaO	0.872	1.3992	1.2201	1.00	1.2201	1.2346	0.0218	1.3548	-16.1160	-0.2183	-0.2183	0.0271	-3.5063
Fe2O3	6.549	1.4297	7.4845	1.00	7.4845	7.5735	0.0469	2.9186	15.5000	0.4524	0.4524	-0.0584	7.2646
FeO	N/A	1.2865	1.6904	1.00	1.6904	1.7105	0.0235	1.4652	-14.6090	-0.2140	-0.2140	0.0293	-3.4373
MgO	1.089	1.8583	1.8059	1.00	1.8059	1.8274	0.0448	2.7897	-13.8880	-0.3874	-0.3874	0.0558	-1.2216
MnO	1.071	1.2912	1.3829	1.00	1.3829	1.3983	0.0195	1.2140	-14.8710	-0.1805	-0.1805	0.0243	-2.8990
Na2O	12.326	1.3480	16.6154	1.04	17.3339	16.8130	0.2797	17.4159	-28.8150	-5.0184	-5.0184	0.3483	-80.5879
Li2O	1.988	2.1525	4.2792	1.00	4.2792	4.3301	0.1432	8.9189	-22.7400	-2.0282	-2.0282	0.1784	-32.5692
K2O	0.422	1.2728	0.5370	1.00	0.5370	0.5434	0.0072	0.4478	-14.3470	-0.0642	-0.0642	0.0090	-1.0313
SiO2	22.122	2.1393	47.3256	1.02	48.3647	47.8883	0.8049	50.1256	5.5900	0.9987	0.9987	0.0000	14.4321
Cr2O3	0.000	1.4616	0.0000	1.00	0.0000	0.0000	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000	0.0000
B2O3	3.485	3.2201	11.2220	1.00	11.2220	11.3555	0.1812	10.0378	-9.9300	-0.9987	-0.9987	0.0000	-16.0081
UO2		1.1344	0.0000		0.0000	0.0000	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000	0.0000
ThO2		1.1376	0.0000		0.0000	0.0000	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000	0.0000
SnO	0.000	1.1826	0.0000		0.0000	0.0000	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000	0.0000
ZnO	0.338	1.3508	0.4578	1.00	0.4578	0.4634	0.0037	0.2314	45.1000	0.1044	0.1044	0.0083	1.6781
TiO2	0.396	1.6680	0.6605	1.00	0.6605	0.6684	0.0083	0.5148	15.9900	0.0823	0.0823	0.0206	1.3219
K2O	0.031	1.2046	0.0377	1.00	0.0377	0.0382	0.0004	0.0248	-41.7350	-0.0104	-0.0104	0.0005	-0.1670
CaO	0.004	1.0602	0.0042	1.00	0.0042	0.0043	0.0000	0.0000	-46.8200	-0.0004	-0.0004	0.0000	-0.0070
Sn2O3		1.1970	0.0000		0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.000	2.2910	0.0000	1.00	0.0000	0.0000	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000	0.0000
Na2O3		1.1660	0.0000		0.0000	0.0000	0.0000	0.0000	-26.3200	0.0000	0.0000	0.0000	0.0000
La2O3	0.243	1.1728	0.2850	1.00	0.2850	0.2884	0.0009	0.0545	-31.1400	-0.0170	-0.0170	0.0016	-0.2724
Y2O3		1.2899	0.0000		0.0000	0.0000	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000	0.0000
B2O	0.000	1.1185	0.0000	1.00	0.0000	0.0000	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000	0.0000
P2O	0.000	1.0772	0.0000		0.0000	0.0000	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000	0.0000
CaO2		1.2284	0.0000		0.0000	0.0000	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000	0.0000
Mn2O3	0.000	1.5003	0.0000	1.00	0.0000	0.0000	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000	0.0000
ZnO	0.194	1.2447	0.2415	1.00	0.2415	0.2443	0.0030	0.1848	-2.4000	-0.0044	-0.0044	0.0037	-0.0712
CaO	0.000	1.2518	0.0000	1.00	0.0000	0.0000	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000	0.0000
Fe2+/Fe3+	0.251												

SUMS

53.023

98.8249

100.7744

100.0000

1.6058

100.0000

SUM + pH SI

SUM + pH B

pH =

-7.5324

-7.5324

-7.5324

-7.5324

-7.5324

ALK/SIO2 =

0.526

ALK + B2O3/SIO2 =

6.726

B2O3/SIO2 =

0.200

VISCOSITY @TEMP(°C)

17.484

LIQUIDUS RATIO =

0.056

LIQUIDUS (°C) =

928

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

	ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	FACTORS FOR CORRECTION		BIAS WAS CORRECT	OXIDE WT%	NORMOXIDE WT%	M.W.	MOLE FRACTION	MOLE % NORMOXIDE	COMPONENT FREEENERGY	FREEENERGY HYDRATION	NEO	KCAL/KG
					CORRECTION	BIAS WAS CORRECT										
Al2O3	Na2O2 DISS/MCP	1.779	1.8995	3.3614	1.05	1.05	3.5420	3.3976	101.9600		0.3347	2.1595	3.0400	0.0856	-0.0432	1.0581
CaO	MW DISS/MCP	0.881	1.3992	1.2327	1.00	1.00	1.2327	1.2460	56.0794		0.0220	1.3664	-16.1160	-0.2202	0.0273	-3.5425
Fe2O3	MW DISS/MCP	6.437	1.4297	7.4277	1.00	1.00	7.4277	7.5077	159.6922		0.0465	2.8914	15.5000	0.4482	-0.0576	7.2095
FeO	REDOX	N/A	1.2865	1.5974	1.00	1.00	1.5974	1.6146	71.8464		0.0222	1.3821	-14.6090	-0.2019	0.0276	-3.2481
MgO	MW DISS/MCP	1.073	1.6583	1.7794	1.00	1.00	1.7794	1.7985	40.3114		0.0441	2.7439	-13.8880	-0.3811	0.0549	-8.1302
MnO	MW DISS/MCP	1.051	1.2612	1.3571	1.00	1.00	1.3571	1.3717	70.9374		0.0191	1.1892	-14.8710	-0.1768	0.0238	-2.8449
Na2O	MW DISS/MCP	12.017	1.3480	16.1989	1.04	1.04	16.8993	16.3734	61.9790		0.2727	16.9495	-28.8150	-4.8840	0.3390	-70.5676
Li2O	MW DISS/MCP	1.947	2.1525	4.1909	1.00	1.00	4.1909	4.2360	29.8774		0.1403	8.7198	-22.7400	-1.9828	0.1744	-31.8975
NO	MW DISS/MCP	0.421	1.2726	0.5356	1.00	1.00	0.5356	0.5415	74.7094		0.0072	0.4458	-14.3470	-0.0640	0.0089	-1.0289
SiO2	Na2O2 DISS/MCP	22.569	2.1393	48.2819	1.02	1.02	49.3419	48.8018	60.0848		0.8212	51.0488	5.5900	0.9855	0.0000	16.0149
Cr2O3	MW DISS/MCP	0.000	1.4616	0.0000	1.00	1.00	0.0000	0.0000	151.9874		0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	Na2O2 DISS/MCP	3.516	3.2201	11.3219	1.00	1.00	11.3219	11.4438	69.6204		0.1626	10.1091	-9.9300	-1.0038	0.0000	-16.1485
UO2			1.1344	0.0000			0.0000	0.0000	270.0388		0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2			1.1379	0.0000			0.0000	0.0000	264.0400		0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	MW DISS/MCP	0.000	1.1826	0.0000			0.0000	0.0000	103.6194		0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZnO	MW DISS/MCP	0.327	1.3508	0.4417	1.00	1.00	0.4417	0.4465	123.2188		0.0036	0.2228	45.1000	0.1005	0.0089	1.3167
TiO2	MW DISS/MCP	0.386	1.6680	0.6438	1.00	1.00	0.6438	0.6508	79.8988		0.0081	0.5009	15.9900	0.0801	0.0200	1.2885
K2O	MW DISS/AA	0.034	1.2046	0.0408	1.00	1.00	0.0408	0.0413	94.2034		0.0004	0.0268	-41.7350	-0.0112	0.0005	-0.1809
CaO	MW DISS/AA	0.004	1.0602	0.0043	1.00	1.00	0.0043	0.0044	281.8094		0.0000	0.0010	-46.8200	-0.0004	0.0000	-0.0072
SnO2			1.1970	0.0000			0.0000	0.0000	291.4982		0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	MW DISS/MCP	0.000	2.2910	0.0000	1.00	1.00	0.0000	0.0000	141.9370		0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3			1.1660	0.0000			0.0000	0.0000	336.4782		0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Y2O3	MW DISS/MCP	0.228	1.1728	0.2874	1.00	1.00	0.2874	0.2703	325.8100		0.0008	0.0510	-31.1400	-0.0159	0.0015	-0.2556
B2O	MW DISS/MCP	0.000	1.2699	0.0000			0.0000	0.0000	225.8082		0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
PbO	MW DISS/MCP	0.000	1.1165	0.0000	1.00	1.00	0.0000	0.0000	153.3394		0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
CaO2	MW DISS/MCP	0.000	1.2284	0.0000			0.0000	0.0000	223.1900		0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
NaO3	MW DISS/MCP	0.000	1.5003	0.0000	1.00	1.00	0.0000	0.0000	172.1200		0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
ZnO	MW DISS/MCP	0.202	1.2447	0.2514	1.00	1.00	0.2514	0.2541	143.9382		0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
O2O	MW DISS/MCP	0.000	1.2518	0.0000	1.00	1.00	0.0000	0.2541	81.3900		0.0031	0.1921	-2.4000	-0.0048	0.0038	-0.0741
Fe2+/Fe3+		0.239		0.0000			0.0000	0.0000	78.5454		0.0000	0.0000	1.7900	0.0000	0.0000	0.0000

SUMS 52.872 98.8346 100.8756 100.0000 1.8087 100.0000 SUM + pH SI SUM + pH B pH = -7.2569 -7.2569 -7.2569

ALK/SIO2 = 0.503
ALK+ B2O3/SIO2 = 0.701
B2O3/SIO2 = 0.198
VISCOSITY @TEMP(°C) = 20.752
LIQUIDUS RATIO = 0.954
LIQUIDUS (°C) = 918

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

FACTORS FOR

ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	BIAS 3/AS CORRECT CORRECTION	BIAS 3/AS CORRECT OXIDE WT%	NORM OXIDE WT%	M.W.	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY	FREE ENERGY HYDRATION	NEO	KCAL/KG
Al2O3	1.910	1.8895	3.6089	1.05	3.8028	3.6970	101.9600	0.0373	2.3663	3.0400	0.0719	-0.0473	1.1338
CaO	0.820	1.3992	1.1473	1.00	1.1473	1.1722	56.0784	0.0205	1.2980	-16.1160	-0.2092	0.0260	-3.2972
Fe2O3	7.063	1.4297	8.3043	1.00	8.3043	8.4838	159.6922	0.0520	3.2992	15.5000	0.5114	-0.0660	8.0603
FeO	N/A	1.2865	1.6141	1.00	1.6141	1.6490	71.8484	0.0225	1.4253	-14.6090	-0.2082	0.0285	-3.2820
MgO	1.037	1.6583	1.7197	1.00	1.7197	1.7568	40.3114	0.0427	2.7065	-13.8860	-0.3759	0.0541	-5.9245
MnO	1.020	1.2912	1.3170	1.00	1.3170	1.3455	70.9374	0.0186	1.1778	-14.8710	-0.1752	0.0236	-2.7610
Na2O	11.640	1.3480	15.9907	1.04	16.3892	16.0300	61.9790	0.2641	16.7563	-28.6150	-4.8283	0.3351	-78.1028
Li2O	1.868	2.1525	4.0209	1.00	4.0209	4.1078	29.8774	0.1346	8.5363	-22.7400	-1.9416	0.1708	-30.6033
NaO	0.394	1.2726	0.5014	1.00	0.5014	0.5122	74.7094	0.0067	0.4258	-14.3470	-0.0611	0.0085	-0.9629
SiO2	22.126	2.1393	47.3342	1.02	48.3734	48.3575	60.0848	0.8051	51.0785	5.5900	1.0158	0.0000	18.0083
Cr2O3	0.000	1.4616	0.0000	1.00	0.0000	0.0000	151.9974	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	3.342	3.2201	10.7616	1.00	10.7616	10.9942	69.6204	0.1548	9.8070	-9.9300	-0.9738	0.0000	-15.3493
Li2O		1.1344	0.0000		0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2		1.1379	0.0000		0.0000	0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SiO	0.000	1.1828	0.0000		0.0000	0.0000	103.6194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZnO	0.515	1.3508	0.6957	1.00	0.6957	0.7107	123.2188	0.0056	0.3582	45.1000	0.1615	0.0143	2.5462
TiO2	0.369	1.8680	0.6155	1.00	0.6155	0.6288	79.8988	0.0077	0.4887	15.9900	0.0781	0.0195	1.2318
K2O	0.036	1.2046	0.0432	1.00	0.0432	0.0442	94.2034	0.0005	0.0291	-41.7350	-0.0122	0.0006	-0.1916
CaO	0.000	1.0602	0.0000	1.00	0.0000	0.0000	281.8094	0.0000	0.0000	-46.8200	0.0000	0.0000	0.0000
Si2O3		1.1870	0.0000		0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.000	2.2910	0.0000	1.00	0.0000	0.0000	141.9370	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3		1.1650	0.0000		0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Li2O3	0.222	1.1728	0.2604	1.00	0.2604	0.2660	325.8100	0.0008	0.0507	-31.1400	-0.0158	0.0015	-0.2488
Y2O3		1.2699	0.0000		0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.000	1.1165	0.0000	1.00	0.0000	0.0000	153.3394	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
FeO	0.000	1.0772	0.0000		0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2		1.2284	0.0000		0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
NaO9	0.000	1.5003	0.0000	1.00	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.200	1.2447	0.2489	1.00	0.2489	0.2543	81.3800	0.0031	0.1841	-2.4000	-0.0047	0.0039	-0.0734
CaO	0.000	1.2516	0.0000	1.00	0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0.216												
SUMS	52.582		97.8837		99.7953	100.0000		1.5782	100.0000		-6.9673	0.5731	-109.8164
ALK/SiO2 =		0.496				TEST=			SUM + pH Si		-6.9673		
ALK+ B2O3/SiO2 =		0.688				TIME=			SUM + pH B		-6.9673		
B2O3/SiO2 =		0.192							pH =				
VISCOSITY @TEMP(°C)		21.759				9 A/V =							
LIQUIDUS RATIO =		0.062											
LIQUIDUS (°C) =		946											

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

GLASS ID= 3-MISC-A

FACTORS FOR

ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	BIAS AS CORRECT CORRECTION	NORMOXIDE WT%	MW.	MOLE FRACTION	NORMOXIDE MOLE %	COMPONENT FREEENERGY	FREEENERGY HYDRATION	NBO	KCAL/KG
Al2O3												
Na2O2 DISS/MCP	1.740	1.895	3.2877	1.05	3.4040	101.9600	0.0340	2.1634	3.0400	0.0658	-0.0433	1.0329
CaO	0.855	1.392	1.983	1.00	1.983	56.0784	0.0213	1.3583	-16.1160	-0.2189	0.0272	-3.4380
Fe2O3	6.292	1.427	7.3255	1.00	7.3255	159.6922	0.0459	2.9208	15.5000	0.4527	-0.0584	7.1102
FeO	N/A	1.2865	1.5029	1.00	1.5029	71.8464	0.0209	1.3319	-14.8090	-0.1946	0.0268	-3.0560
MgO	1.060	1.6583	1.7578	1.00	1.7578	40.3114	0.0436	2.7764	-13.8880	-0.3856	0.0555	-6.0559
MnO	1.031	1.2912	1.3312	1.00	1.3312	70.9374	0.0188	1.1849	-14.8710	-0.1777	0.0239	-2.7907
Na2O2 DISS/MCP	11.913	1.3480	16.0587	1.04	16.7531	61.9790	0.2703	17.2107	-28.8150	-4.9593	0.3442	-77.8876
Li2O	1.919	2.1525	4.1306	1.00	4.1306	29.8774	0.1383	8.8029	-22.7400	-2.0018	0.1761	-31.4388
NO	0.393	1.2726	0.5001	1.00	0.5001	74.7084	0.0087	0.4262	-14.3470	-0.0612	0.0085	-0.9604
Na2O2 DISS/MCP	21.868	2.1393	46.7822	1.02	47.8093	60.0848	0.7957	50.6637	5.5900	0.9578	0.0000	15.0396
Cr2O3	0.000	1.4616	0.0000	1.00	0.0000	151.9974	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
Na2O2 DISS/MCP	3.453	3.2201	11.1190	1.00	11.1190	69.6204	0.1587	10.1890	-9.9300	-1.0098	0.0000	-15.8591
Li2O		1.1344	0.0000		0.0000	270.0388	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000
TiO2		1.1379	0.0000		0.0000	264.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SO	0.000	1.1928	0.0000		0.0000	103.6194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZrO2	0.308	1.3508	0.4174	1.00	0.4174	123.2188	0.0034	0.2157	45.1000	0.0973	0.0086	1.5277
TiO2	0.375	1.6680	0.8255	1.00	0.8255	79.8988	0.0078	0.4985	15.9900	0.0797	0.0199	1.2518
R2O	0.031	1.2048	0.0372	1.00	0.0372	94.2034	0.0004	0.0252	-41.7350	-0.0105	0.0005	-0.1649
CaO	0.004	1.0602	0.0043	1.00	0.0043	281.8084	0.0000	0.0010	-48.8200	-0.0005	0.0000	-0.0072
SiO2		1.1970	0.0000		0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.000	2.2910	0.0000	1.00	0.0000	141.8370	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3		1.1660	0.0000		0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Li2O3	0.225	1.1728	0.2639	1.00	0.2639	325.8100	0.0008	0.0516	-31.1400	-0.0161	0.0015	-0.2522
Y2O3		1.2699	0.0000		0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
B2O	0.000	1.1165	0.0000		0.0000	153.3394	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
RO	0.000	1.0772	0.0000	1.00	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2		1.2284	0.0000		0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MgO3	0.000	1.5003	0.0000	1.00	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZrO	0.195	1.2447	0.2427	1.00	0.2427	81.3800	0.0030	0.1899	-2.4000	-0.0046	0.0038	-0.0716
CaO	0.000	1.2518	0.0000	1.00	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+Fe3+	0.228											

SIMS

98.5832

98.4813

1.5705

0.5948

-116.0202

0.514

0.715

0.261

16.932

0.055

919

TEST=

TIME=

8A/V=

SUM + pH Si

SUM + pH B

pH=

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

FACTORS FOR CORRECTION														
	ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	BIAS AS CORRECT		NORMALIZE WT%	MW	MOLE FRACTION	NORMALIZE MOLE %	COMPONENT FREE ENERGY		NBO	KCAL/KG
					CORRECTION	OXIDE WT%					FREE ENERGY	HYDRATION		
Al2O3	Na2O2 DISS/CP	1.722	1.8895	3.2537	1.05	3.4285	3.3640	101.9600	0.0336	2.1368	3.0400	0.0850	-0.0428	1.0222
CaO	MW DISS/CP	0.895	1.3992	1.2523	1.00	1.2523	1.2947	56.0784	0.0223	1.4202	-16.1160	-0.2289	0.0284	-3.5988
Fe2O3	MW DISS/CP	6.370	1.4297	7.2916	1.00	7.2916	7.5387	159.6922	0.0457	2.9038	15.5000	0.4501	-0.0581	7.0773
FeO	REDX	N/A	1.2865	1.6336	1.00	1.6336	1.6891	71.8464	0.0227	1.4482	-14.8090	-0.2113	0.0289	-3.3220
MgO	MW DISS/CP	1.061	1.6593	1.7595	1.00	1.7595	1.8191	40.3114	0.0436	2.7759	-13.8880	-0.3855	0.0555	-8.0616
MnO	MW DISS/CP	1.041	1.2912	1.3438	1.00	1.3438	1.3893	70.9374	0.0189	1.2047	-14.8710	-0.1792	0.0241	-2.8170
Na2O	MW DISS/CP	12.037	1.3480	16.2252	1.04	16.9288	16.7752	61.9780	0.2731	17.3692	-28.8150	-5.0049	0.3474	-78.6951
Li2O	MW DISS/CP	1.936	2.1525	4.1675	1.00	4.1675	4.3087	29.8774	0.1395	8.8711	-22.7400	-2.0173	0.1774	-31.7189
NO	MW DISS/CP	0.409	1.2726	0.5202	1.00	0.5202	0.5378	74.7084	0.0070	0.4428	-14.3470	-0.0835	0.0089	-0.9991
SiO2	Na2O2 DISS/CP	21.887	2.1393	46.3950	1.02	47.4136	47.9678	60.0848	0.7881	50.1888	5.5900	0.9010	0.0000	14.1675
Cr2O3	MW DISS/CP	0.000	1.4818	0.0000	1.00	0.0000	0.0000	151.8974	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	Na2O2 DISS/CP	3.441	3.2201	11.0804	1.00	11.0804	11.4558	69.8204	0.1592	10.1220	-8.9300	-1.0051	0.0000	-15.8040
UO2			1.1344	0.0000	1.00	0.0000	0.0000	270.0388	0.0000	0.0000	-6.8000	0.0000	0.0000	0.0000
ThO2			1.1378	0.0000	1.00	0.0000	0.0000	284.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SnO	MW DISS/CP	0.000	1.1826	0.0000	1.00	0.0000	0.0000	103.8194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZnO	MW DISS/CP	0.323	1.3508	0.4382	1.00	0.4382	0.4510	123.2188	0.0035	0.2251	45.1000	0.1015	0.0090	1.5965
TiO2	MW DISS/CP	0.394	1.6680	0.6584	1.00	0.6584	0.6788	79.8988	0.0082	0.5225	15.9900	0.0835	0.0209	1.3136
K2O	MW DISS/AA	0.032	1.2048	0.0385	1.00	0.0385	0.0399	94.2034	0.0004	0.0260	-41.7350	-0.0109	0.0005	-0.1708
Ca2O	MW DISS/AA	0.004	1.0602	0.0042	1.00	0.0042	0.0044	281.8094	0.0000	0.0010	-46.8200	-0.0004	0.0000	-0.0070
Sn2O3			1.1970	0.0000	1.00	0.0000	0.0000	281.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	MW DISS/CP	0.000	2.2910	0.0000	1.00	0.0000	0.0000	141.9370	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3			1.1680	0.0000	1.00	0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3	MW DISS/CP	0.254	1.1728	0.2978	1.00	0.2978	0.3080	325.8100	0.0009	0.0581	-31.1400	-0.0181	0.0017	-0.2847
Y2O3			1.2698	0.0000	1.00	0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
B2O	MW DISS/CP	0.000	1.1165	0.0000	1.00	0.0000	0.0000	153.3394	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
FeO	MW DISS/CP	0.000	1.0772	0.0000	1.00	0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2			1.2284	0.0000	1.00	0.0000	0.0000	172.1290	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
Mn2O3	MW DISS/CP	0.000	1.5003	0.0000	1.00	0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	MW DISS/CP	0.294	1.2447	0.3655	1.00	0.3655	0.3778	81.3800	0.0045	0.2857	-2.4000	-0.0069	0.0057	-0.1078
CaO	MW DISS/CP	0.000	1.2518	0.0000	1.00	0.0000	0.0000	70.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+		0.249												

ALK/SiO2 = 0.523
ALK + B2O3/SiO2 = 0.725
B2O3/SiO2 = 0.202
VISCOSITY @TEMP(°C) = 17.361
LIQUIDUS RATIO = 0.055
LIQUIDUS (°C) = 924
NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

(SPREADSHEET REVISION 5.0, OCTOBER 23, 1990)

CLASS ID= 2-B-A

FACTORS FOR

	ANALYTIC	ELEMENT	GRAV	OXIDE	BIAS 3/AS CORRECT	NORM OXIDE	M.W.	FRACTION	MOLE	NORM OXIDE	COMPONENT	FREE ENERGY	NBD	KCAL/KG
	TECHNIQUE	WT%	FACTOR	WT%	CORRECTION	OXIDE WT%	WT%				FREE ENERGY	HYDRATION		
Al2O3	Na2O2 DISS/MCP	1.785	1.8995	3.3728	1.05	3.5539	3.4285	101.9600	0.0348	2.1772	3.0400	0.0862	-0.0435	1.0596
CaO	MW DISS/MCP	0.822	1.3992	1.1501	1.00	1.1501	1.1692	56.0794	0.0205	1.2811	-16.1160	-0.2065	0.0258	-3.3053
Fe2O3	MW DISS/MCP	6.163	1.4297	7.0210	1.00	7.0210	7.1372	159.6922	0.0440	2.7463	15.5000	0.4257	-0.0549	6.8147
FeO	REDUX	N/A	1.2865	1.6110	1.00	1.6110	1.6377	71.8464	0.0224	1.4006	-14.6090	-0.2046	0.0280	-3.2758
MO	MW DISS/MCP	1.029	1.6583	1.7058	1.00	1.7058	1.7341	40.3114	0.0423	2.6432	-13.8880	-0.3671	0.0529	-5.8769
MO	MW DISS/MCP	1.005	1.2912	1.2962	1.00	1.2962	1.3197	70.9374	0.0183	1.1431	-14.8710	-0.1700	0.0229	-2.7215
Na2O	MW DISS/MCP	11.697	1.3480	15.7676	1.04	16.4493	16.0284	61.9790	0.2654	16.5779	-28.8150	-4.7769	0.3316	-76.4754
Li2O	MW DISS/MCP	1.874	2.1525	4.0342	1.00	4.0342	4.1008	29.8774	0.1350	8.4342	-22.7700	-1.9179	0.1687	-30.7048
NO	MW DISS/MCP	0.403	1.2728	0.5129	1.00	0.5129	0.5213	74.7094	0.0069	0.4286	-14.3470	-0.0615	0.0086	-0.9849
SiO2	Na2O2 DISS/MCP	22.958	2.1393	49.1140	1.02	50.1924	49.9284	60.0848	0.8354	52.1793	5.5900	1.1093	0.0000	17.7589
Cr2O3	MW DISS/MCP	0.000	1.4816	0.0000	1.00	0.0000	0.0000	151.9974	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	Na2O2 DISS/MCP	3.486	3.2201	11.1609	1.00	11.1609	11.3455	69.6204	0.1603	10.0135	-8.9300	-0.9943	0.0000	-15.9188
Li2O			1.1344	0.0000		0.0000	0.0000	270.0388	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000
TiO2			1.1379	0.0000		0.0000	0.0000	284.0400	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SO	MW DISS/MCP	0.000	1.1826	0.0000		0.0000	0.0000	103.6194	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZnO	MW DISS/MCP	0.314	1.3508	0.4237	1.00	0.4237	0.4308	123.2188	0.0034	0.2148	45.1000	0.0969	0.0086	1.5510
TiO2	MW DISS/MCP	0.379	1.6680	0.6315	1.00	0.6315	0.6420	79.8988	0.0079	0.4937	15.9900	0.0789	0.0197	1.2838
FeO	MW DISS/AA	0.032	1.2048	0.0381	1.00	0.0381	0.0387	94.2034	0.0004	0.0252	-41.7350	-0.0105	0.0005	-0.1686
CaO	MW DISS/AA	0.004	1.0602	0.0043	1.00	0.0043	0.0044	281.8094	0.0000	0.0010	-46.8200	-0.0005	0.0000	-0.0072
SiO2			1.1970	0.0000		0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
FeO3			2.2910	0.0000		0.0000	0.0000	141.9370	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3			1.1660	0.0000		0.0000	0.0000	336.4782	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
Li2O3			1.1728	0.2850	1.00	0.2850	0.2897	325.8100	0.0003	0.0546	-31.1400	-0.0170	0.0016	-0.2724
Y2O3			1.2699	0.0000		0.0000	0.0000	225.8082	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
B2O	MW DISS/MCP	0.000	1.1165	0.0000		0.0000	0.0000	153.3394	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
FeO	MW DISS/MCP	0.000	1.0772	0.0000		0.0000	0.0000	223.1900	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2			1.2284	0.0000		0.0000	0.0000	172.1200	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
NaO3			1.5003	0.0000		0.0000	0.0000	143.9382	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	MW DISS/MCP	0.194	1.2447	0.2418	1.00	0.2418	0.2458	91.3900	0.0030	0.1854	-2.4000	-0.0045	0.0037	-0.0712
CaO			1.2518	0.0000		0.0000	0.0000	79.5454	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+Fe3+														
SUMS		52.367		98.3728	100.3141	100.0000	100.0000	1.8008	100.0000				0.5739	-111.3349

ALK/SIO2 = 0.480
ALK+ B2O3/SIO2 = 0.672
B2O3/SIO2 = 0.192
VISCOSITY @TEMP(°C) = 26.057
LIQUIDUS RATIO = 0.050
LIQUIDUS (°C) = 993

NOTE LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FE2O3 (OCTOBER 23, 1990)

ANALYTIC TECHNIQUE	ELEMENT WT%	GRAV FACTOR	OXIDE WT%	BIAS FOR CORRECTION		BIAS CORRECT OXIDE WT%	NORM OXIDE WT%	MW	MOLE FRACTION	NORM OXIDE MOLE %	COMPONENT FREE ENERGY		NEO	KCAL/KG
Al2O3	1.783	1.8895	3.3690	1.05	3.5499	3.4080	101.9600	0.0348	0.0348	2.1682	3.0400	0.0659	-0.0434	1.0584
CaO	0.888	1.3992	1.2439	1.00	1.2439	1.2578	56.0794	0.0222	0.0222	1.3813	16.1160	-0.2226	0.0276	-3.5747
Fe2O3	6.599	1.4297	7.7587	1.00	7.7587	7.8440	159.6922	0.0486	0.0486	3.0258	15.5000	0.4690	-0.0605	7.5307
FeO	N/A	1.2865	1.5080	1.00	1.5080	1.5248	71.8464	0.0210	0.0210	1.3071	14.6090	-0.1910	0.0281	-3.0684
MgO	1.086	1.6583	1.8009	1.00	1.8009	1.8207	40.3114	0.0447	0.0447	2.7821	13.8890	-0.3864	0.0556	-8.2045
MgO	1.067	1.2912	1.3777	1.00	1.3777	1.3928	70.9374	0.0194	0.0194	1.2095	14.8710	-0.1799	0.0242	-2.8882
Na2O	12.349	1.3480	16.6465	1.04	17.3662	16.8294	61.9790	0.2802	0.2802	17.4490	28.8150	-5.0279	0.3490	-80.7382
Li2O	1.973	2.1525	4.2469	1.00	4.2469	4.2935	29.8774	0.1421	0.1421	8.9519	22.7400	-2.0129	0.1770	-32.3235
NO	0.428	1.2728	0.5447	1.00	0.5447	0.5507	74.7094	0.0073	0.0073	0.4540	14.3470	-0.0651	0.0091	-1.0460
SiO2	22.218	2.1393	47.5287	1.02	48.5702	48.0489	60.0848	0.8084	0.8084	50.3402	5.5900	0.9194	0.0000	14.7630
Cr2O3	0.000	1.4816	0.0000	1.00	0.0000	0.0000	151.9974	0.0000	0.0000	0.0000	37.3600	0.0000	0.0000	0.0000
B2O3	3.471	3.2201	11.1770	1.00	11.1770	11.2998	69.6204	0.1605	0.1605	9.9976	-8.9300	-0.9928	0.0000	-15.8418
Li2O	1.1344	1.1344	0.0000	1.00	0.0000	0.0000	270.0388	0.0000	0.0000	0.0000	-8.8000	0.0000	0.0000	0.0000
ThO2	1.1379	1.1379	0.0000	1.00	0.0000	0.0000	264.0400	0.0000	0.0000	0.0000	-2.5330	0.0000	0.0000	0.0000
SiO	0.000	1.1826	0.0000	1.00	0.0000	0.0000	103.6194	0.0000	0.0000	0.0000	-24.4000	0.0000	0.0000	0.0000
ZrO2	0.340	1.3508	0.4594	1.00	0.4594	0.4644	123.2188	0.0037	0.0037	0.2322	45.1000	0.1047	0.0093	1.8813
TiO2	0.401	1.6680	0.6882	1.00	0.6882	0.6755	79.8988	0.0084	0.0084	0.5208	15.9900	0.0833	0.0208	1.3373
K2O	0.029	1.2046	0.0345	1.00	0.0345	0.0348	94.2034	0.0004	0.0004	0.0228	-41.7350	-0.0095	0.0005	-0.1526
Ce2O	0.004	1.0602	0.0043	1.00	0.0043	0.0044	281.8094	0.0000	0.0000	0.0010	-46.8200	-0.0004	0.0000	-0.0072
Sn2O3	0.000	1.1970	0.0000	1.00	0.0000	0.0000	291.4982	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000	0.0000
P2O5	0.000	2.2910	0.0000	1.00	0.0000	0.0000	141.9370	0.0000	0.0000	0.0000	-53.6200	0.0000	0.0000	0.0000
Na2O3	0.000	1.1660	0.0000	1.00	0.0000	0.0000	336.4782	0.0000	0.0000	0.0000	-28.3200	0.0000	0.0000	0.0000
La2O3	0.240	1.1728	0.2818	1.00	0.2818	0.2849	325.8100	0.0009	0.0009	0.0539	-31.1400	-0.0168	0.0016	-0.2694
Y2O3	0.000	1.2699	0.0000	1.00	0.0000	0.0000	225.8082	0.0000	0.0000	0.0000	-12.9500	0.0000	0.0000	0.0000
BaO	0.000	1.1165	0.0000	1.00	0.0000	0.0000	153.3394	0.0000	0.0000	0.0000	-30.5700	0.0000	0.0000	0.0000
PbO	0.000	1.0772	0.0000	1.00	0.0000	0.0000	223.1900	0.0000	0.0000	0.0000	-8.8100	0.0000	0.0000	0.0000
CaO2	0.000	1.2284	0.0000	1.00	0.0000	0.0000	172.1200	0.0000	0.0000	0.0000	11.3450	0.0000	0.0000	0.0000
MnO3	0.000	1.5003	0.0000	1.00	0.0000	0.0000	143.9362	0.0000	0.0000	0.0000	-21.7500	0.0000	0.0000	0.0000
ZnO	0.213	1.2447	0.2851	1.00	0.2851	0.2860	81.3800	0.0033	0.0033	0.2028	-2.4000	-0.0049	0.0041	-0.0782
CoO	0.000	1.2518	0.0000	1.00	0.0000	0.0000	79.5454	0.0000	0.0000	0.0000	1.7900	0.0000	0.0000	0.0000
Fe2+/Fe3+	0.218													
SIMS	53.088		99.9132		100.8574	100.0000		1.8058	100.0000				0.8011	-119.9197

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

-7.4679

SUM + pH SI

SUM + pH B

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

pH =

TEST=

TIME=

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

100.8574

100.0000

TEST=

TIME=

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

100.8574

100.0000

TEST=

TIME=

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

100.8574

100.0000

TEST=

TIME=

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

99.9132

100.0000

TEST=

TIME=

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

8 A/V =

0.523

0.722

0.199

17.578

0.057

927

927

927

927

9

ANALYTIC		ELEMENT		GRAV		OXIDE		BIAS & AS CORRECT		NORM OXIDE		MW		MOLE		NORM OXIDE		COMPONENT		FREE ENERGY		NEO		KCAL/KG	
TECHNIQUE		WT%		FACTOR		WT%		CORRECTION		OXIDE WT%		WT%		FRACTION		MOLE %		FREE ENERGY		HYDRATION					
Al2O3	Na2O2 DISS/ICP	1.830		1.8895		3.4578		1.05	3.6435	3.4001		101.9600		0.0357		2.1788		3.0400		0.0662		-0.0436		1.0863	
CaO	MW DISS/ICP	1.060		1.3992		1.4825		1.00	1.4825	1.4577		56.0794		0.0284		1.6119		-16.1160		-0.2598		0.0322		-4.2602	
Fe2O3	MW DISS/ICP	7.022		1.4297		8.2560		1.00	8.2560	8.1183		159.6822		0.0517		3.1524		15.5000		0.4886		-0.0630		8.0135	
PbO	REDUX	N/A		1.2865		1.6047		1.00	1.6047	1.5779		71.8464		0.0223		1.3619		-14.6090		-0.1990		0.0272		-3.2629	
MgO	MW DISS/ICP	1.189		1.6583		1.9717		1.00	1.9717	1.9388		40.3114		0.0489		2.9824		-13.8880		-0.4142		0.0596		-8.7929	
MnO	MW DISS/ICP	1.149		1.2912		1.4836		1.00	1.4836	1.4588		70.9374		0.0208		1.2752		-14.8710		-0.1896		0.0255		-3.1101	
Na2O	MW DISS/AA	12.500		1.3480		16.8500		1.00	16.8500	16.5889		61.9790		0.2719		16.5769		-28.8150		-4.7766		0.3315		-78.3383	
Li2O	MW DISS/ICP	2.125		2.1525		4.5741		1.00	4.5741	4.4978		29.8774		0.1531		9.3349		-22.7400		-2.1227		0.1867		-34.8137	
NO	MW DISS/ICP	0.471		1.2726		0.5998		1.00	0.5998	0.5898		74.7094		0.0080		0.4895		-14.3470		-0.0702		0.0098		-1.1518	
SiO2	Na2O2 DISS/ICP	22.554		2.1393		48.2498		1.02	48.3091	47.4449		60.0848		0.8207		50.0393		5.5900		0.8917		0.0000		14.6238	
Cr2O3	MW DISS/ICP	0.000		1.4616		0.0000		1.00	0.0000	0.0000		151.9874		0.0000		0.0000		37.3600		0.0000		0.0000		0.0000	
B2O3	Na2O2 DISS/ICP	3.520		3.2201		11.3348		1.00	11.3348	11.1457		69.8204		0.1628		9.9271		-9.9300		-0.9858		0.0000		-18.1668	
Li2O				1.1344		0.0000				0.0000		270.0388		0.0000		0.0000		-8.0000		0.0000		0.0000		0.0000	
ThO2				1.1379		0.0000				0.0000		264.0400		0.0000		0.0000		-2.5330		0.0000		0.0000		0.0000	
SiO	MW DISS/ICP	0.000		1.1828		0.0000				0.0000		103.8194		0.0000		0.0000		-24.4000		0.0000		0.0000		0.0000	
ZrO2	MW DISS/ICP	0.353		1.3508		0.4763		1.00	0.4763	0.4683		123.2188		0.0038		0.2357		45.1000		0.1083		0.0094		1.7433	
TiO2	MW DISS/ICP	0.434		1.6880		0.7239		1.00	0.7239	0.7118		79.8988		0.0091		0.5525		15.9900		0.0883		0.0221		1.4488	
K2O	MW DISS/AA	0.031		1.2048		0.0369		1.00	0.0369	0.0362		94.2034		0.0004		0.0238		-41.7350		-0.0100		0.0005		-0.1633	
CaO	MW DISS/AA	0.004		1.0602		0.0042		1.00	0.0042	0.0042		281.8094		0.0000		0.0009		-46.8200		-0.0004		0.0000		-0.0070	
SiO2O3				1.1970		0.0000				0.0000		291.4982		0.0000		0.0000		0.0000		0.0000		0.0000		0.0000	
P2O5	MW DISS/ICP	0.000		2.2910		0.0000		1.00	0.0000	0.0000		141.9370		0.0000		0.0000		-53.6200		0.0000		0.0000		0.0000	
Na2O3				1.1860		0.0000				0.0000		336.4782		0.0000		0.0000		-28.3200		0.0000		0.0000		0.0000	
Li2O3	MW DISS/ICP	0.282		1.1728		0.3304		1.00	0.3304	0.3249		325.8100		0.0010		0.0618		-31.1400		-0.0193		0.0019		-0.3158	
Y2O3				1.2699		0.0000				0.0000		225.8082		0.0000		0.0000		-12.9500		0.0000		0.0000		0.0000	
B2O	MW DISS/ICP	0.000		1.1165		0.0000		1.00	0.0000	0.0000		153.3394		0.0000		0.0000		-30.5700		0.0000		0.0000		0.0000	
PbO	MW DISS/ICP	0.000		1.0772		0.0000				0.0000		223.1900		0.0000		0.0000		-8.8100		0.0000		0.0000		0.0000	
CaO2				1.2284		0.0000				0.0000		172.1200		0.0000		0.0000		11.3450		0.0000		0.0000		0.0000	
NaCO3	MW DISS/ICP	0.000		1.5003		0.0000		1.00	0.0000	0.0000		143.9382		0.0000		0.0000		-21.7500		0.0000		0.0000		0.0000	
ZrO	MW DISS/ICP	0.209		1.2447		0.2801		1.00	0.2601	0.2558		81.3800		0.0032		0.1948		-2.4000		-0.0047		0.0039		-0.0767	
ClO	MW DISS/ICP	0.000		1.2518		0.0000		1.00	0.0000	0.0000		79.5454		0.0000		0.0000		1.7800		0.0000		0.0000		0.0000	
Fe2+Fe3+																									
SLMS		54.732				101.6965			102.9416	100.0000				1.9400		100.0000		SUM + pH SJ		-7.4111		0.8038		-121.5440	
										TEST=								SUM + pH B		-7.4111					
										TIME=								pH =							
										SA/V=															

0.518

ALK/SHO2 =

ALK= B2O3/SHO2 =

B2O3/SHO2 =

VISCOSITY @TEMP(°C)

LIQUIDUS RATIO =

LIQUIDUS (°C) =

9.38

NOTE: LIQUIDUS AND VISCOSITY FORMULAS CHANGED TO CALCULATE ALL FE AS FeO3 (OCTOBER 23, 1990)

APPENDIX III Multielement Solution Standard Analysis - Researcher I

Element	Concentration of Multielement Standard ug/mL	Run before Samples-1 ug/mL	Run before Samples-2 ug/mL	Run after 5 Samples-1 ug/mL	Run after 5 Samples-2 ug/mL	Run after 10 Samples-1 ug/mL	Run after 10 Samples-2 ug/mL	Run after 15 Samples-1 ug/mL	Run after 15 Samples-2 ug/mL
Na (ICP)	50.10	49.20	49.62	49.00	49.55	49.55	49.52	49.39	49.34
Na (AA)		46.42	45.00	47.18	46.35	49.31	52.13	51.09	52.13
Si	50.10	44.68	44.96	45.41	45.17	45.34	45.05	45.15	44.91
B	20.00	19.64	19.74	19.81	19.75	19.76	19.73	19.61	19.60
K	10.00	9.65	9.52	9.56	9.50	9.52	9.65	9.79	9.61
Li	10.00	9.86	9.93	9.96	9.94	9.94	9.92	9.89	9.88
Al	4.06	3.25	3.42	3.37	3.36	3.33	3.27	3.32	3.29
Fe	3.98	4.19	4.21	4.21	4.21	4.21	4.20	4.19	4.19

Element	Concentration of Multielement Standard ug/mL	Average Bias before Leachate Analysis ug/mL	Average Bias after 5 Leachate Analyses ug/mL	Average Bias after 10 Leachate Analyses ug/mL	Average Bias after 15 Leachate Analyses ug/mL
Na (ICP)	50.10	-0.69	-0.82	-0.57	-0.74
Na (AA)		-4.39	-3.34	0.62	1.51
Si	50.10	-5.28	-4.81	-4.91	-5.07
B	20.00	-0.31	-0.22	-0.25	-0.39
K	10.00	-0.42	-0.47	-0.42	-0.30
Li	10.00	-0.10	-0.05	-0.07	-0.12
Al	4.06	-0.62	-0.70	-0.76	-0.76
Fe	3.98	0.22	0.23	0.22	0.21

Element	Run after 20 Samples-2 ug/mL	Run after 20 Samples-2 ug/mL	Run after 25 Samples-2 ug/mL	Run after 25 Samples-2 ug/mL	Run after 30 Samples-2 ug/mL	Run after 30 Samples-2 ug/mL	Run after 35 Samples-2 ug/mL	Run after 35 Samples-2 ug/mL	Run after 40 Samples-2 ug/mL	Run after 40 Samples-2 ug/mL
Na (ICP)	49.52	49.61	49.37	49.11	49.09	48.98	49.20	49.08	50.03	50.01
Na (AA)	50.94	49.90	50.35	50.20	49.30	49.45	49.77	52.25	50.35	50.79
Si	45.16	45.06	45.00	44.53	44.61	44.26	44.66	44.32	45.53	45.35
B	19.63	19.67	19.57	19.45	19.38	19.36	19.49	19.46	19.92	19.90
K	9.56	9.52	9.56	9.42	9.64	9.67	9.66	9.92	9.54	9.57
Li	9.89	9.93	9.87	9.84	9.83	9.82	9.86	9.85	9.94	9.93
Al	3.25	3.28	3.29	3.25	3.25	3.23	3.27	3.24	3.25	3.25
Fe	4.20	4.21	4.18	4.16	4.14	4.13	4.15	4.14	4.21	4.21

Element	Average Bias after 20 Leachate Analyses ug/mL	Average Bias after 25 Leachate Analyses ug/mL	Average Bias after 30 Leachate Analyses ug/mL	Average Bias after 35 Leachate Analyses ug/mL	Average Bias after 40 Leachate Analyses ug/mL
Na (ICP)	-0.53	-0.86	-1.07	-0.96	-0.08
Na (AA)	0.32	0.18	-0.73	0.91	0.47
Si	-4.99	-5.34	-5.67	-5.61	-4.66
B	-0.35	-0.49	-0.63	-0.52	-0.09
K	-0.46	-0.51	-0.35	-0.21	-0.45
Li	-0.09	-0.15	-0.18	-0.14	-0.07
Al	-0.60	-0.79	-0.82	-0.81	-0.81
Fe	0.22	0.19	0.15	0.16	0.23

END

**DATE
FILMED**

3 / 26 / 93