WSRC-RP-92-037, REV 0

ERRORS OF DWPF FRIT ANALYSIS - FINAL REPORT (U)

by R. F. Schumacher

Westinghouse Savannah River Company
Savannah River Site
Aiken, South Carolina 29808

WSRC-RP--92-37

DE93 003372

NOV 27 1992

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

WESTINGHOUSE
SAVANNAH RIVER COMPANY

WSRC-RP-92-37
Rev. 0

Key Words: DWPF
glass frit, analyses
Retention Time: Permanent
cc: E.W. Holtzscheiter, 773-A
N.E. Bibler, 773-A
J.T. Carter, 704-T
L.F. Landon, 704-T
C.T. Randall, 704-T
K.G. Brown, 704-T
C.E. Coffey, 773-A
R.S. Beck, 704-S
J.F. Sproull, 704-S
L.J. Jones, 704-S
Glass Tech. (9)
SRL Records (4)

To: M.J. Plodinec, 773-A

From: R.F. Schumacher, 773-42A January 24, 1992
RFS 1/22/92

ERRORS OF DWPF FRIT ANALYSIS - FINAL REPORT - (U)

SUMMARY

Glass frit will be a major raw material for the operation of the Defense Waste Processing Facility. The frit will be controlled by certificate of conformance and a confirmatory analysis by a commercial laboratory. The following effort provides additional quantitative information on the variability of frit analyses at two commercial laboratories.

Identical Samples of IDMS Frit 202 were chemically analyzed at two commercial laboratories and at three different times over a period of four months. Similar samples were analyzed once by SRL's ADS laboratory. The vendor also supplied an analysis for one of the samples. The variability of the oxide determinations was shown to be critical to the frit acceptance process. All of the laboratories provided reasonably good chemical analyses. However, the CELS laboratory consistently provided a better level of precision. The standard deviations of the Monarch analyses for individual elements were two to ten times greater than the CELS analyses. The variabilities of the results were analyzed and it was concluded that a single CELS laboratory analysis was sufficient to confirm the certification of SRL Frit 202 with a high level of confidence. The Monarch analyses were more variable and twice as many analyses would be required to obtain similar levels of confidence. It is strongly suggested that the CELS laboratory be used as a sole source supplier of the chemical analyses for DWPF Frit until such time as it is shown that other laboratories can provide similar levels of analytical precision.

M.J. Plodinec, 773-A
Authorized Derivative Classifier

The SRL-ADS analyses, after correction with the reference standard and normalization, provided confirmatory information, but did not detect the low silica level in one of the frit samples.

A methodology utilizing elliptical limits for confirming the certificate of conformance was introduced and recommended for use when the analysis values are close to the specification limits. It was also suggested that the lithia specification limits could be reduced as long as CELS is used to confirm the analysis.

INTRODUCTION

The Waste Acceptance Preliminary Specifications, (WAPS)¹ require that the Defense Waste Processing Facility (DWPF) control the consistency of the waste glass product. As described in the Waste Form Compliance Plan (WCP)² this will be achieved through control of the chemical composition of the glass product. Since the glass frit purchased by the DWPF will constitute approximately two thirds of the waste glass product, control of the composition of the frit is an important part of meeting the chemical composition specifications.

Current plans are to control the composition of the frit through the procurement specifications and chemical analyses of representative lot samples. Until the present effort, little data has been available on the errors involved in the chemical analyses of frit. The objective of this task is to quantify the errors involved in the chemical analysis of frit and based on this information, to consider modification of the current specification.

The frit specification for the Integrated DWPF Melter System (IDMS) runs was put into the format of an Essential Materials Specification (EMS No. 206) and was used to obtain initial orders of frit for qualification. The composition limits were based on the previous frit procurement specifications and general knowledge of the manufacturer's capabilities. Of the four suppliers evaluated under the EMS 206 specifications, three suppliers provided material which marginally met the specifications. Each of the three materials was at the limit of at least one of the specifications³. A new specification for DWPF Cold Runs was prepared based on the EMS 206 and published as Specification No. OPS-DTE-910003. The chemical portion of the new specification was essentially unchanged. Table 1 is a summary of the chemical portion of the specification, which must be met for each composite sample from each "Lot" of Frit 202. The lot shall be in multiple increments of 5,000 pounds.

The "Total Undesirable Components" is defined as 100 wt% minus the actual analysis of the five major constituents listed below and includes but is not limited to Al, Fe, Mn, Ni, Cr, Pb, Ti, F, and Cl. Additional undesirable components > 0.05 wt% shall be reported along with their amount in the certificate of conformance. The moisture content of each lot of material shall be less than 0.1 wt% and the total reducible material as measured by a "Chemical Oxygen Demand" determination shall be less than 0.1 wt%. In addition, the particle size distribution of each lot of frit must be such that ≥ 99.0 wt% passes through a Tyler 80 mesh screen, and < 10 wt% passes through a Tyler 200 mesh screen. The material must be free flowing.

Table 1
Chemical Composition Specification for Frit 202

Component	Concentration (Wt%)
SiO ₂	77.0 ± 1.0
Na ₂ O	6.0 ± 0.5
B ₂ O ₃	8.0 ± 0.5
Li ₂ O	7.0 ± 0.5
MgO	2.0 ± 0.25

Each lot of material shall have less than the following
undesirable components in the frit.

Chemical	Maximum (Wt.%)
Al	1.0
Fe	0.2
Mn	0.2
Ni	0.2
Cr	0.1
Pb	0.1
Ti	0.15
F	0.05
Cl	0.05
Total Undesirable Components	< 2.25 wt%

The specification presently requires the qualified vendor to obtain a representative sample of frit for each lot of material. One representative sample will be analyzed by the supplier and the analysis delivered as a certificate of conformance. A second sample will be submitted to an independent certified laboratory for a confirmatory analysis.

The chemical analyses will be used to confirm that the lot of frit meets the procurement specification prior to the delivery of the material. When the frit is used in the DWPF process the chemical composition of the frit will be employed in the "Process Composition Control System" (PCCS) to achieve an acceptable chemical composition of the waste-frit- slurry mixture.

The difficulty in meeting the multiple interrelated frit specification limits as previously described in the Frit 202 specification has been discussed by Postles⁴. For example, if there are "n" simultaneous specification limits and each has been established such that it has a false rejection rate of about 0.05 or 5%; then when all "n" components are applied simultaneously, the false rejection rate would be $1-(.95)^n$. This would provide a false rejection rate of 0.226 for n equals 5. In other words, nearly a fourth of the material would be rejected unjustly for the five major limits in the Frit 202 specification. This can be compensated for theoretically by utilizing the simultaneous confidence ellipsoid theory due to Hotelling⁵. In addition, it is believed that elliptical limits provide a more just criteria for acceptance rather than the upper and lower rectangular limit approach. A graphical representation for two components is shown in Figure 1. The area of the ellipse compared to the rectangle was expanded by approximately 25% and the original 1:2 ratio in the limits was maintained. A similar approach was taken for the other specifications and the ratios and resulting areas are presented in Table 2.

Table 2
Ellipsoid Radii Ratios and Expanded Areas

Oxide Pair	Spec. Ratio	Ratio	Ellipse Radii	Rectang. Area	Ellipse Area
SiO ₂ /R ₂ O	2/1 Wt%	2	1.26/0.63 Wt%	2.0 Wt%	2.49Wt%
SiO ₂ /MgO	2/0.5	4	1.26/0.32	1.0	1.27
SiO ₂ /Tot. Maj.	2/2.25	0.89	1.26/1.42	4.5	5.625

It was possible with these specifications to maintain the major silica radius at about 1.26 and increase all the ellipse areas by 25%. The area of the ellipse is π times the product of the major and minor radii of the ellipse.

When the frit is chemically analyzed to determine if it meets the chemical specification, there is a confidence band on either side of the oxide measurement. In order to provide the usual 95% confidence that the analytic value is acceptable, the measured value should be at least two standard deviations inside the ellipse. Conversely when the analytic value is more than two standard deviations outside the ellipse the confidence that the result is not within specification is greater than 95%. When the analysis falls in the region of the ellipse $\pm$ two standard deviations ($\pm 2\sigma$) the conformance to the specification is a matter of probability. A single analysis directly on the ellipse would have a 50:50 chance of being in specification. This concept is graphically presented in Figure 2. As a matter of convenience and based on probability, any value inside the elliptical limit may be assumed to be within specification, while any value outside the ellipse is assumed to be out of specification.

EXPERIMENTAL

Experimental Design

A partially nested experimental design was used to assess the contributions of various sources of uncertainty ⁴. A Reference Standard Frit ⁶, whose chemical composition had been determined to a high level of reliability was included as a control sample. After development of the Reference Frit it was planned to determine the composition of three IDMS frit samples at three commercial laboratories at three different times. The fourth sample would be the Reference Frit sample. A Task Plan⁷ was prepared and included the experimental design shown in Table 3.

Table 3
Planned Design of Experiment

	Lab. 1	Lab. 2	Lab. 3	SRL-ADS
Sample 1	Time 1,2,3	Time 1,2,3	Time 1,2,3	Time 1
Sample 2	"	"	"	"
Sample 3	"	"	"	"
Ref. Stand.	"	"	"	"

Material Acquisition

The Reference Frit standard, a 100 pound sample of SRL Frit 202, was obtained from Ferro Corporation under purchase order number 0402593 and under procurement specification DWPT-QA-89-1019, at procurement level 1. The material was initially glass flake which was ground as a lot to less than 200 mesh powder ($< 74 \mu$) and blended to form a homogeneous sample prior to shipment to SRL in three six gallon metal containers. A sample from the number 1 container was used in this study (E-51768-49-101) as the reference standard glass. This glass was well analyzed chemically and a best estimate of the chemical composition was reported⁶. The best estimate composition is reproduced as Table 4. This estimate was largely based on the high level of reliability obtained from an accumulation of CELS analyses of the reference standard and, to a lesser extent, analyses by other chemical laboratories. The best estimate composition accounts for 99.9 wt% of the metallic oxides. It was felt that any improvement in the analytic chemical composition determination would require an extensive "Round Robin" analyses with little corresponding benefit.

Table 4
Chemical Analysis Frit 202 Reference Frit Standard
(Best Estimate of Chemical Composition - Ref. 6)

Oxide	Wt%	Oxide	Wt%	Oxide	Wt%
SiO ₂	76.6	Na ₂ O	5.9	NiO	<.01
B ₂ O ₃	7.70	Li ₂ O	6.7	PbO	0.01
Al ₂ O ₃	0.40	K ₂ O	0.19	TiO ₂	0.11
Fe ₂ O ₃	0.03	ZrO ₂	0.02	BaO	0.04
CaO	0.12	MnO ₂	<.01	Sb ₂ O ₃	<.1
MgO	2.0	Cr ₂ O ₃	<.01	F	0.03
				Cl	0.01
				CO ₂	<.02
				Total	99.9

Three samples of SRL Frit 202 were obtained as grab samples (approximately 1 pound) from containers of frit ordered for the IDMS runs at TNX. The samples were labeled as E-51768-2 : -1, -2, and -3. The frit was also supplied by Ferro Corporation and markings from the bin identification are presented as Appendix A.

Sample Splitting

The three IDMS samples and the reference standard material were split into twenty identical samples with the Quantachrome Rotary Riffler, Model SRR-2, under procedure GTOP-3-024, Rev. 0. The use of this type of splitter provides an extremely low sample variability due to the rotary splitting process. Table 5 provides the sample number identification.

Table 5
Sample Identification

<u>Sample No.</u>	<u>Identification</u>	<u>Split Sample No.</u>
E-517 68-2-1	IDMS SRL Frit 202 Ferro Corp (7-1-88)	E-51768-98-6 to 25 (Twenty Samples)
E-51768-2-2	IDMS SRL Frit 202 Ferro Corp. (6-30-88)	E-51768-99-6 to 25 (Twenty Samples)
E-51768-2-3	IDMS SRL Frit 202 Ferro Corp. (7-5-88)	E-51768-100- 6 to 25 (Twenty Samples)
E-51768-49-101	Reference Standard Frit 202 (Can 1)	E-51768-101-6 to 25 (Twenty Samples)

Chemical Analysis

From the twenty identical samples of each large frit sample, eight samples were randomly selected and submitted to SRL - Analytic Development Section (ADS) for dissolution and chemical analysis by Inductively Coupled Plasma (ICP) and Atomic Absorption (AA). Eight samples of the 202 Reference Frit standard were included to provide corrections for the SRL-ADS analyses. Previous experiments during the frit qualification studies³ found that approximately 8 to 10 samples provided a reasonably reliable average chemical analysis when the results were bias corrected with a standard and normalized to approximately 100%.

From the remaining twelve samples of each frit, a single random sample for each of the four Frit 202 samples was sent to Corning Engineering Laboratory Services (CELS) and to Monarch Analytical Laboratories (MAL) at three different times i.e., April 6, June 29, and August 6, 1990. One laboratory, Sharp Schurtz Co., declined to bid on this work and was not replaced. These laboratories are among the best analytic laboratories which tend to specialize in glass analysis. The CELS analyses were carried out under purchase order AA10904 and the MAL analyses under AA15342N. Both orders were conducted under QA level 2. It was requested that the laboratories use what they felt were their best analytical methods e.g. ICP, AA, X-ray fluorescence, titrations, specific ion electrodes, etc. for any glass component greater than 0.10 wt%. The expected ranges of elements were provided with the order. Both laboratories were informed that the SiO₂ level exceeded 50 wt%, the Na₂O, B₂O₃, Li₂O, MgO, and Al₂O₃ could be between 1 to 15 wt%. and that the Fe₂O₃, TiO₂, MnO, K₂O, NiO, Cr₂O₃, PbO, F, Cl, were less than 1 wt%. The cost of the Monarch analyses of four samples was \$2320 while the cost of the CELS analyses was \$2220. The final experimental design is shown in Table 6.

Table 6
Experimental Sample Analysis Design

Frit 202 Sample	E-51768-98-	99-	100-	101- (Ref. Std)
SRL - ADS (8 samples)	Time (1)	Time (1)	Time (1)	Time (1)
Corning (CELS) (3 samples)	Time(1,2,3)	Time(1,2,3)	Time(1,2,3)	Time(1,2,3)
Monarch (MAL) (3 samples)	Time(1,2,3)	Time(1,2,3)	Time(1,2,3)	Time(1,2,3)
Vendor (Ferro)	(Cert.Conform.)			

In the past samples of another reference standard, Frit 165, were extensively analyzed at the CELS laboratory. Additional analyses nearly five years later provided an impressive demonstration of the repeatability and consistency of the CELS laboratory. Table 7 provides the comparison of CELS analyses over this five year period.

Table 7
CELS Chemical Analyses of SRL Frit 165

Analysis:		3-15-85		11-22-89		1-11-90		4 Samp.
Oxide	No. Samples	Oxide (Wt%)	Std. Dev.	Oxide (Wt%)	Oxide (Wt%)	Oxide (Wt%)	Oxide (Wt%)	Stand. Dev.
B ₂ O ₃	(16)	9.32	0.064	9.36	9.44	9.37	9.38	0.04
Na ₂ O	(16)	12.16	0.045	12.2	12.1	12.1	12.1	0.05
Li ₂ O	(16)	6.96	0.029	6.87	6.83	6.83	6.81	0.02
MgO	(16)	0.99	0.010	1.00	1.01	1.02	1.02	0.01
ZrO ₂	(16)	0.99	0.017	0.97	0.96	0.98	0.96	0.01
SiO ₂	(10)	68.89	0.075	68.9	68.9	69.3	69.3	0.23
Total		99.31		99.30	99.24	99.6	99.67	0.21

RESULTS AND DISCUSSION

Monarch Analytic Laboratory

The Monarch Analytical Laboratories provided two analyses of each sample sent to them. The original data is presented as Appendix B. In order to compare against the CELS data, the average analyses for each set of two results was obtained and presented as a single value along with the CELS determinations. MAL did not perform a qualitative analysis or determine all of the oxides above 0.10 wt.% as requested. An attempt was made to reduce the variance of the MAL results by correcting with the reference standard, however, this appeared to reduce all of the oxide variability except for silica and since this is the most variable oxide this approach was not used.

Corning Engineering Laboratory Services

CELS conducted an initial qualitative analysis in order to determine the relative amounts of oxides present, then analyzed for all oxides above 0.10 wt%. The results of the CELS and MAL analyses are presented in Tables 8 to 11 with the values outside of the rectangular specifications in " Bold Underline ". It should also be noted that some of the frit samples were out of specification. Comparing the number of oxides analyzed which were outside the rectangular specifications: CELS showed a total of eleven oxide analyses out of specification while the MAL analyses had 19 out of specification. In general, sample 98 appeared to be on the lower limit for boron but within specification. Sample 99 was on the lower limit for lithia but within specification. Sample 100 was out of specification, and below the lower limit on lithia, magnesia, silica and the total of the major oxides. Sample 101, the reference standard, was within specification for all oxides. The average of the values, variance, standard deviation, and relative standard deviations for the data were included in Tables 8 to 11.

The variances for the analyses of each oxide were pooled (summed and divided by n) to form the average standard deviation for the CELS and MAL laboratories. The variances, pooled variance, and average standard deviations, are presented in Table 12. The average standard deviations were similar to those obtained for the 165 Reference Frit (See Table 7). The average standard deviations for the CELS analyses were about 1/7 of the MAL standard deviations. The pooled variance provided an excellent estimate of the standard deviation for the given oxide determination capability for each laboratory. Since the elliptical limits are based on $\pm 2 \sigma$, a listing of 2σ values was included in Table 12. The standard deviations for silica and the total of the major oxide analyses for both laboratories were comparable.

The average standard deviation can be used to estimate the number of analyses required from a specific laboratory for an analysis of a specific oxide. The Student's "t" equation⁸ for the upper and lower confidence limits may be used for this purpose.

$$\text{Upper Limit, Lower Limit} = \bar{x} \pm t (s / \sqrt{n})$$

The difference between the upper and lower 95% confidence limits was chosen to be approximately 0.50 wt% for reasonable discrimination between values. Setting t equal to 3 and solving for n , one obtains the number of analyses as follows:

$$n = 22 t^2 s^2 / (.50)^2 = 144 s^2$$

This equation was solved and presented as the last column in Table 12. In general, it appeared that twice as many analyses would be required from MAL as from CELS. This would require at least twice the cost for verifying the certificate of conformance.

The 2σ values from Table 12 were also used to construct the elliptical limits for the CELS and MAL analyses of the four frit samples. These values are presented in Table 13. Review Figure 2 for the location of the limits for SiO_2 . Figures 3 to 6 summarize the positions of the three analyses for each of the five major oxides from CELS using the elliptical limits. It should be noted that the three analyses for sample 98 are within both the rectangular and elliptical chemical limits for the oxides (Figure 3). The boron level is definitely acceptable. The lithia level for sample 99 (Figure 4) is in the region of uncertainty where there is approximately a 50:50 probability of being acceptable. As long as all other specifications were within the limits this material would be acceptable. For sample 100 (Figure 5), the low levels of silica, lithium, and magnesium are quite obvious. This material could be rejected. Sample 101 (Figure 6) is within specification for all five oxides. The "Best Estimate" values are included on this figure for comparison and it can be seen that the CELS average value is very near the best estimate. Figure 7 plots the ellipse comparing the silica analysis to the sum of major oxides. Sample 100 is again outside of the acceptable region.

In order to provide a comparison with the MAL analyses, the analyses of samples 98 and 101 are presented in Figures 8 and 9. The effect of the increased variability in the analyses is immediately apparent. The acceptance of the lithia and boron oxide are in some doubt for sample 98 and the low silica level obtained for the reference standard sample 101 makes it difficult to assure the acceptance of this material. Both samples 98 and 101 were acceptable by the CELS analyses and variability. It is believed that the MAL analysis is low in silica and this also affects the sum of the majors which is particularly low for this sample. If in the future, the variability of the measurements from MAL could not be reduced, it would be more difficult to confirm the acceptability of these types of frit and they could be rejected.

The lithia analysis by CELS was quite reproducible and had an average standard deviation of .037 wt %. Reviewing previous data on frit qualification it is apparent that all suppliers provided frit on the low half of the specification. That is, all analyses for acceptable samples were between 6.0 to 7.0 wt %, while the specification was between 6.5 to 7.5 wt%. It appears probable that the frit vendors are controlling the level of lithia to the low end of the specification. The reason for this is the cost of the lithia in this glass probably exceeds the sum of the cost of all the other raw materials. If the frit with higher lithia levels would significantly improve the waste product and CELS is used to confirm the analysis, it should be possible to reduce the specification limits for lithia to between 6.75 to 7.25 wt%.

Analysis of Variance for CELS and MAL Analyses

Because this was a statistically designed study, it was possible to develop an analysis of variance for each oxide and laboratory. The results of these statistical analyses are presented in Tables 14 to 16 and they reinforce the importance of obtaining as low a variability in the chemical analyses as possible. The results which were outside of the specifications were again in "Bold Underline". The analysis of variance for the silica results from both laboratories (CELS and MAL) produced an "F" value which indicates a significant difference between the sample means for each sample⁸. The F value provided more than a 99% confidence that the sample means for silica for each sample were indeed different. The Corning F value was slightly higher than the MAL F value. The CELS data indicates that sample 100 is below the specification for SiO₂, while the MAL analyses indicates that samples 99, 100, and 101 may be below the specification. A brief table of confidence levels and F values is outlined in the right quadrant of each Table.

The averages of the B₂O₃ contents were within specification, however, two of the MAL analyses gave values just below the limit. The ANOV indicated that the difference in samples was very significant for the CELS analyses while the F value for the MAL analyses was not significant. In other words, the samples were not significantly different when the analysis error was considered.

All of the values and averages for the Na₂O content were within the specifications, however again the differences in the means observed by the CELS analysis were significant while the MAL were not able to detect a significant difference in the samples.

The lithia levels were at the lower limit of the specification for all of the samples. That is all values obtained were between 6.0 and 7.0 wt%. Samples 99 and 100 for the CELS analyses were at or below the limit of 6.50 wt%. All four samples analyzed by MAL had at least one value outside the specification. The CELS analysis provided significant differences between the samples while the MAL did not. The average values were similar.

The magnesia level from both laboratories for sample 100 was outside the specification. Both laboratories indicated significant differences between the samples and provided similar results.

An analysis of variance was carried out on the total of the major oxides. Both laboratories were able to detect the differences in the samples and both indicated that sample No. 100 was outside the specification.

The variance between laboratories was not calculated as it has already been shown that the variability between labs is significant with CELS having much less variability.

SRL-ADS

The ICP data obtained from the SRL ADS laboratory is presented in Appendix C. The element weight percent data obtained from the eight analyses of the reference standard (E-51768-101-XX), as presented on page one, were averaged and used to calculate the oxide weight percent of the major components as shown on page two. The total oxide weight percent outputs should have summed to almost 100% but only 91.37 wt% was reported. A first attempt to normalize the data to 100% was not effective, so the data from the best estimate analysis of the reference standard was used to develop correction factors for each oxide. These correction factors (outlined) were then used to adjust the data obtained for the next three SRL Frit 202 analyses. This procedure was similar to that used to correct and normalize data for Frit 202 Qualification studies³, and based on the 165 Frit standard.

The ICP data from the SRL ADS analyses of the three IDMS frit samples are presented in Appendix C on pages 3, 5, & 7. This data was used to calculate oxide weight percentages on pages 4, 6, & 8. The data was then corrected with the analysis of the reference standard and then normalized to 100%. These results agree closely to the analytical results from the two commercial laboratories. The SRL-ADS results are compared to the other analyses in Tables 16 to 19. The SRL-ADS analyses were unable to show that sample 100 was below the silica specification. The other oxide analyses were reasonably good predictors that the oxides were either within or outside the specifications and may aid in determining acceptance of frit materials, if required.

CONCLUSIONS

The results of this investigation provided the following conclusions:

1. The CELS laboratory has demonstrated a superior level of precision during this and other frit analyses. The CELS laboratory provided oxide analyses of Frit 202 with less variability than the MAL laboratory. This was demonstrated with Analysis of Variance and calculation of the number of samples required for an analysis. In order to provide results with similar levels of confidence, it would require at least twice the number of analyses at MAL as at CELS and this would essentially double the cost of confirming the certificate of conformance. The CELS laboratory should be strongly considered as a sole source vendor for the analysis of DWPF frit until such time as other vendors can demonstrate a similar level of precision.
2. The elliptical limits with $\pm 2 \sigma$ regions should be employed to confirm acceptance of DWPF frit. These graphical representations were particularly helpful when the analyzed values were near the specification limits.
3. The SRL-ADS laboratory can be used to support the certificate of conformance, but will require the inclusion of standard material and at least eight or ten multiple analyses. The reference standard (E-51768-49-101) should be used for this purpose.

4. It should be emphasized that both the CELS and MAL laboratories are two of the finest glass analytical laboratories in the United States and while comparisons were made it should not be construed that there was any intent to criticize the capabilities of any of the facilities, including SRL-ADS or the frit vendors.

5. Future specification should consider the reduction in the acceptable limits from ± 0.50 wt% to ± 0.25 wt%. Both the vendors and the CELS analytic laboratory appear to have sufficient control to maintain this limit.

REFERENCES

1. U.S. Department of Energy, Office of Civilian Radioactive Waste Management, "Waste-Form Acceptance Preliminary Specifications for Vitrified High Level Waste Forms", New Version, June 1991.
2. WSRC-SW4-6 DWPF Waste Form Compliance Plan, Rev. 0, March 1990. (WSRC-RP-90-367. March 28, 1990).
3. R.F. Schumacher, "DWPF Frit Qualification-Summary", WSRC-TR-90-160, April 6, 1990.
4. Private Communication, R.L. Postles to R.F. Schumacher, "Round Robin Study of Assay Uncertainty.", March 28, 1989.
5. H. Hotelling, "The Generalization of Student's Ratio", Ann. Math. Stat., 2, 1931, P360-7.
6. R.F. Schumacher, "Errors of DWPF Frit Analysis - Reference Standard -II", WSRC-RP-90-1219, October 22, 1990.
7. R.F. Schumacher, "Quality Assurance/Assessment Plan - Errors of DWPF Frit Analyses-(U)", WSRC-RP-89-50, May 1, 1989.
8. R.G. Steel & J.H. Torrie, "Principles and Procedures of Statistics", McGraw-Hill Co. New York, 1960.

FIGURE 1. Graphical Representation of Portions of the Specification and 25% Area Expansion of Limits Due to Multiple Oxide Requirements.

FIGURE 2. Graphical Representation of Expanded Specifications Due to Multiple Limits and Inclusion of 95% Confidence Bands.

Sample No. E-51768-98

FIGURE 3. CELS CHEMICAL ANALYSIS OF FRIT 202 SAMPLE E-51768-98

FIGURE 4. CELS CHEMICAL ANALYSES OF FRIT 202 SAMPLE NO. E-51768-99

FIGURE 5. CELS CHEMICAL ANALYSES OF FRIT 202 SAMPLE NO. E-51768-100

-18-

● "BEST ESTIMATE" VALUE FOR
REFERENCE STANDARD

FIGURE 6. CELS CHEMICAL ANALYSES OF FRIT 202 SAMPLE NO. E-51768-101

FIGURE 7. Graphical Representation of the Total Major Oxides with Variability Limits due to Uncertainty of Three Determinations by CELS

Sample No. E-51768-98

FIGURE 8. MAL CHEMICAL ANALYSIS OF FRIT 202 SAMPLE E-51768-98

Sample No. E-51768-98

● BEST ESTIMATE VALUE, REFERENCE STANDARD.

FIGURE 9. MAL CHEMICAL ANALYSIS OF FRIT 202 SAMPLE E-51768-101

CORNING CELS ANALYSIS GLASS #98

OXIDE: Wt%	4/25/90 98 #9	6/29/90 98 #19	8/21/90 98 #17	Average	Variance	Std. Dev.	RSD %*
K2O	0.13	0.12	0.12	0.123	0.000	0.006	4.68%
Li2O	6.67	6.69	6.69	6.683	0.000	0.012	0.17%
Na2O	5.88	5.92	5.90	5.900	0.000	0.020	0.34%
Al2O3	0.24	0.24	0.24	0.240	0.000	0.000	0.00%
B2O3	7.55	7.52	7.57	7.547	0.001	0.025	0.33%
CaO	0.13	0.13	0.13	0.130	0.000	0.000	0.00%
MgO	2.13	2.13	2.13	2.130	0.000	0.000	0.00%
TiO2	0.096	0.096	0.096	0.096	0.000	0.000	0.00%
SiO2	76.8	76.7	76.78	76.760	0.003	0.053	0.07%
Total	99.03	98.96	99.07	99.020	0.003	0.036	0.06%
Total = Sum of Majors							
RSD=Std. Dev./Mean Range = Max-Min							

MONARCH ANALYSIS GLASS #98

OXIDE	5/3/90 98 #15 Avg. of 2	7/18/90 98 #23 Avg. of 2	8/31/90 98 #6 Avg. of 2	Average	Variance	Std. Dev.	RSD %*
OXIDE: Wt%							
K2O		0.12	0.12	0.120	0.000	0.000	0.00%
Li2O	6.72	6.48	6.79	6.663	0.026	0.163	2.44%
Na2O	5.92	5.74	5.83	5.830	0.008	0.090	1.54%
Al2O3	0.19	0.22	0.22	0.210	0.000	0.017	8.25%
B2O3	7.44	7.87	7.41	7.573	0.066	0.257	3.40%
CaO		0.12	0.13	0.125	0.000	0.007	5.66%
MgO	2.06	2.12	2.2	2.127	0.005	0.070	3.30%
SiO2	76.64	76.57	76.63	76.613	0.001	0.038	0.05%
Total	98.78	98.78	98.86	98.807	0.002	0.046	0.05%

TABLE 8 CELS & MAL CHEMICAL ANALYSES OF SRL FRIT-202 (E-51768-98)

CELS ANALYSIS GLASS #99

OXIDE: Wt%	4/25/90 99#10	6/29/90 99#18	8/21/90 99#19	Average	Variance - 98	Std. Dev. - 99	RSD %
K ₂ O	0.37	0.36	0.35	0.360	0.000	0.010	2.78%
Li ₂ O	6.51	6.47	6.46	6.480	0.001	0.026	0.41%
Na ₂ O	5.97	5.97	5.97	5.970	0.000	0.000	0.00%
Al ₂ O ₃	0.30	0.32	0.32	0.313	0.000	0.012	3.69%
B ₂ O ₃	7.79	7.74	7.78	7.770	0.001	0.026	0.34%
CaO	0.26	0.24	0.23	0.243	0.000	0.015	6.28%
MgO	1.94	1.96	1.98	1.960	0.000	0.020	1.02%
TiO ₂	0.31	0.31	0.32	0.313	0.000	0.006	1.84%
SiO ₂	76.2	76.3	76.4	76.300	0.010	0.100	0.13%
Total	98.41	98.44	98.59	98.480	0.009	0.096	0.10%

Total = Sum of Majors

RSD=Std. Dev./Mean
Range = Max-Min

MONARCH ANALYSIS GLASS #99

OXIDE	5/3/90 99#20 Avg. of 2	7/18/90 99#12 Avg. of 2	8/31/90 99#6 Avg. of 2	Average	Variance - 98	Std. Dev. - 99	RSD %
OXIDE: Wt%							
K ₂ O		0.34	0.35	0.345	0.000	0.007	2.05%
Li ₂ O	6.44	6.19	6.6	6.410	0.043	0.207	3.22%
Na ₂ O	5.86	5.8	5.92	5.860	0.004	0.060	1.02%
Al ₂ O ₃	0.28	0.28	0.29	0.283	0.000	0.006	2.04%
B ₂ O ₃	7.70	8.02	7.78	7.833	0.028	0.167	2.13%
CaO		0.22	0.22	0.220	0.000	0.000	0.00%
MgO	1.90	1.94	1.99	1.943	0.002	0.045	2.32%
SiO ₂	76.00	75.96	75.92	75.960	0.002	0.040	0.05%
Total	97.9	97.91	98.21	98.007	0.031	0.176	0.18%

TABLE 9. CELS & MAL CHEMICAL ANALYSIS OF SRL FRIT-202 (E-51768-99)

CORNING ANALYSES GLASS # 100

OXIDE:	4/25/90 100#18	6/29/90 100#16	8/21/90 100#12	Average	Variance	Std. Dev.	RSD %
K2O	0.55	0.55	0.54	0.547	0.000	0.006	1.06%
Li2O	6.37	6.26	6.25	6.293	0.004	0.067	1.06%
Na2O	5.86	5.87	5.85	5.860	0.000	0.010	0.17%
Al2O3	0.45	0.47	0.47	0.463	0.000	0.012	2.49%
B2O3	7.93	7.97	7.96	7.953	0.000	0.021	0.26%
CaO	0.40	0.40	0.40	0.400	0.000	0.000	0.00%
MgO	1.63	1.61	1.63	1.623	0.000	0.012	0.71%
TiO2	0.47	0.47	0.47	0.470	0.000	0.000	0.00%
SiO2	75.8	75.4	75.7	75.633	0.043	0.208	0.28%
Total	97.59	97.11	97.39	97.363	0.058	0.241	0.25%

RSD=Std Dev./Mean
Range = Max-Min

Total = Sum of Majors

MONARCH ANALYSIS GLASS# 100

OXIDE	5/3/90 100#20 Avg. of 2	7/18/90 100#6 Avg. of 2	8/31/90 100#22 Avg of 2	Average	Variance	Std. Dev.	RSD %
K2O		0.54	0.54	0.540	0.000	0.000	0.00%
Li2O	6.26	5.96	6.40	6.207	0.051	0.225	3.62%
Na2O	5.76	5.64	5.79	5.730	0.006	0.079	1.39%
Al2O	0.44	0.44	0.44	0.440	0.000	0.000	0.00%
B2O3	7.95	8.13	7.78	7.953	0.031	0.175	2.20%
CaO		0.39	0.40	0.395	0.000	0.007	1.79%
MgO	1.56	1.58	1.66	1.600	0.003	0.053	3.31%
SiO2	75.65	75.54	75.70	75.630	0.007	0.082	0.11%
Total	97.18	96.85	97.33	97.120	0.060	0.246	0.25%

TABLE 10 CELS & MAL CHEMICAL ANALYSES OF SRL FRIT-202 (E-51768-100)

CELS Analysis #101 Reference Standard

OXIDE:	4/25/90 101#25	6/29/90 101#17	8/21/90 101#13	Average	Variance	Std. Dev.	RSD %
K ₂ O	0.21	0.19	0.18	0.193	0.000	0.015	7.90%
Li ₂ O	6.63	6.65	6.65	6.643	0.000	0.012	0.17%
Na ₂ O	5.88	5.88	5.87	5.877	0.000	0.006	0.10%
Al ₂ O ₃	0.38	0.42	0.43	0.410	0.001	0.026	6.45%
B ₂ O ₃	7.60	7.58	7.63	7.603	0.001	0.025	0.33%
CaO	0.11	0.12	0.11	0.113	0.000	0.006	5.09%
MgO	2.03	2.03	2.03	2.030	0.000	0.000	0.00%
TiO ₂	0.11	0.11	0.11	0.110	0.000	0.000	0.00%
SiO ₂	76.4	76.5	76.8	76.567	0.043	0.208	0.27%
Total	98.54	98.64	98.98	98.720	0.053	0.231	0.23%

Total = Sum of Majors

MONARCH GLASS ANALYSIS GLASS#101 Reference Standard

OXIDE	5/3/90 101#15 Avg. of 2	7/18/90 101#22 Avg. of 2	8/31/90 101#14 Avg. of 2	Average	Variance	Std. Dev.	RSD %
K ₂ O		0.18	0.18	0.180	0.000	0.000	0.00%
Li ₂ O	6.60	6.39	6.83	6.607	0.048	0.220	3.33%
Na ₂ O	5.77	5.76	5.83	5.787	0.001	0.038	0.65%
Al ₂ O ₃	0.34	0.34	0.35	0.343	0.000	0.006	1.68%
B ₂ O ₃	7.64	7.89	7.56	7.697	0.030	0.172	2.24%
CaO	1.95	0.10	0.12	0.110	0.000	0.014	12.86%
MgO	76.01	2.02	2.07	2.013	0.004	0.060	2.99%
SiO ₂		75.49	75.96	75.820	0.082	0.287	0.38%
Total	97.97	97.55	98.25	97.923	0.124	0.352	0.36%

TABLE 11. CELS & MAL CHEMICAL ANALYSES OF SRL FRIT-202 (E-512768-101)

- 25 -

CORNING ANALYSES

OXIDE:	Variance - 9 8	Variance - 9 9	Variance - 1 0 0	Variance - 1 0 1	Average Variance (pooled)	Avg. SD $\sqrt{(\text{Var})}$	2 SIGMA (Best Est.)	Est.No. Anal. Required UL-LL = .25
K ₂ O	0.000	0.000	0.000	0.000	0.000	0.010		
Li ₂ O	0.000	0.001	0.004	0.000	0.001	0.037	0.07	0.19
Na ₂ O	0.000	0.000	0.000	0.000	0.000	0.012	0.02	0.02
Al ₂ O ₃	0.000	0.000	0.000	0.001	0.000	0.016		
B ₂ O ₃	0.001	0.001	0.000	0.001	0.001	0.024	0.05	0.09
CaO	0.000	0.000	0.000	0.000	0.000	0.008		
MgO	0.000	0.000	0.000	0.000	0.000	0.012	0.02	0.02
TiO ₂	0.000	0.000	0.000	0.000	0.000	0.003		
SiO ₂	0.003	0.010	0.043	0.043	0.025	0.158	0.32	3.58
Total Maj.	0.003	0.009	0.058	0.053	0.031	0.176	0.35	4.45

MONARCH ANALYSES

OXIDE	Variance - 9 8	Variance - 9 9	Variance - 1 0 0	Variance - 1 0 1	Average Variance (pooled)	Avg. SD $\sqrt{(\text{Var})}$	2 SIGMA (Best Est.)	Est.No. Anal. Required UL-LL = .25
K ₂ O	0.000	0.000	0.000	0.000	0.000	0.004		
Li ₂ O	0.026	0.043	0.051	0.048	0.042	0.205	0.41	6.05
Na ₂ O	0.008	0.004	0.006	0.001	0.005	0.070	0.14	0.70
Al ₂ O ₃	0.000	0.000	0.000	0.000	0.000	0.010		
B ₂ O ₃	0.066	0.028	0.031	0.030	0.039	0.196	0.39	5.55
CaO	0.000	0.000	0.000	0.000	0.000	0.009		
MgO	0.005	0.002	0.003	0.004	0.003	0.058	0.12	0.48
SiO ₂	0.001	0.002	0.007	0.082	0.023	0.152	0.30	3.31
Total	0.002	0.031	0.060	0.124	0.054	0.233	0.47	7.83

TABLE 12. COMPARISON OF VARIANCE OF OXIDE DETERMINATION WITH TIME

CELS										
Oxide Specs	2sigma	-2sigma	Lo Ellipse	+2sigma	Lower Spec	Target	Upper Spec	-2sigma	Up. Ellipse	+2sigma
SiO2	0.32	75.42	75.74	76.06	76	77	78	77.94	78.26	78.58
Li2O	0.07	6.3	6.37	6.44	6.5	7	7.5	7.56	7.63	7.7
Na2O	0.02	5.35	5.37	5.39	5.5	6	6.5	6.61	6.63	6.65
B2O3	0.05	7.32	7.37	7.42	7.5	8	8.5	8.58	8.63	8.68
MgO	0.02	1.66	1.68	1.7	1.75	2	2.25	2.3	2.32	2.34
Total Ox.	0.35	97.1	97.45	97.8	97.75	98.88		99.95	100.3	100.65
MAL										
Oxide Specs	2sigma	-2sigma	Lo Ellipse	+2sigma	Lower Spec	Target	Upper Spec	-2sigma	Up. Ellipse	+2sigma
SiO2	0.3	75.44	75.74	76.04	76	77	78	77.96	78.26	78.56
Li2O	0.41	5.96	6.37	6.78	6.5	7	7.5	7.22	7.63	8.04
Na2O	0.14	5.23	5.37	5.51	5.5	6	6.5	6.49	6.63	6.77
B2O3	0.39	6.98	7.37	7.76	7.5	8	8.5	8.24	8.63	9.02
MgO	0.12	1.56	1.68	1.8	1.75	2	2.25	2.2	2.32	2.44
Total Ox.	0.47	96.98	97.45	97.92	97.75	98.88		99.83	100.3	100.77

TABLE 13. ELLIPTICAL LIMITS WITH 2 SIGMA LIMITS

CELS ANALYSIS										MAL ANALYSIS									
t = 4 n = 3										t = 4 n = 3									
Treatment	98	99	100	101	Total	98	99	100	101 Total	Treatment	98	99	100	101 Total					
	5.88	5.97	5.86	5.88		5.92	5.86	5.76	5.77		5.92	5.86	5.76	5.77					
	5.92	5.97	5.87	5.88		5.74	5.80	5.64	5.76		5.74	5.80	5.64	5.76					
	5.90	5.97	5.85	5.87		5.83	5.92	5.79	5.83		5.83	5.92	5.79	5.83					
Sum Xij	17.7	17.91	17.58	17.63	70.82	17.49	17.58	17.19	17.36	69.62	17.49	17.58	17.19	17.36					
Sum (Xij) ²	104.43	106.92	103.02	103.61	417.98	101.98	103.03	98.51	100.46	403.98	101.98	103.03	98.51	100.46					
CTj	104.43	106.92	103.02	103.61	417.98	101.97	103.02	98.50	100.46	403.94	101.97	103.02	98.50	100.46					
Sum Sqj	0.001	0.000	0.000	0.000	0.001	0.016	0.007	0.013	0.003	0.039	0.016	0.007	0.013	0.003					
Sum Sq j/n-1	0.000	0.000	0.000	0.000		0.008	0.004	0.006	0.001		0.008	0.004	0.006	0.001					
s	0.020	0.000	0.010	0.006		0.090	0.060	0.079	0.038		0.090	0.060	0.079	0.038					
Mean	5.90	5.97	5.86	5.88		5.83	5.86	5.73	5.79		5.83	5.86	5.73	5.79					
CT	417.96					403.91					403.91								
Source of Var.	df	Sum Sqs	Mean Sq.	F		Source of Var.	df	Sum Sqs	Mean Sq.	F	Source of Var.	df	Sum Sqs	Mean Sq.	F				
Total	11	0.02	0.01	52.75 > 99%		Total	11	0.07	0.01	1.97 Not Sig.	Total	11	0.07	0.01	1.97 Not Sig.				
Treat.	3	0.02	0.01			Treat.	3	0.03	0.01		Treat.	3	0.03	0.01					
Error	8	0.00	0.00			Error	8	0.04	0.00		Error	8	0.04	0.00					

TABLE 15 ANALYSIS OF VARIANCE FOR Na2O and Li2O

MAL ANALYSIS

[illegible]

CELS ANALYSIS

Treatment	t = 4 n = 3	98	MgO Content	101 Total
	2.13	1.94	1.63	2.03
	2.13	1.96	1.61	2.03
	2.13	1.98	1.63	2.03
Sum Xij	6.39	5.88	4.87	6.09
Sum (Xij) ²	13.61	11.53	7.91	12.36
CTj	13.61	11.52	7.91	12.36
Sum Sq.i	0.000	0.001	0.000	0.000
Sum Sq j/n-1	0.000	0.000	0.000	0.000
s	0.000	0.020	0.012	0.000
Mean	2.13	1.96	1.62	2.03
CT	44.97			
Source of Var.	df	Sum Sqs	Mean Sq.	F
Total	11	0.44		
Treat.	3	0.43	0.14	1086.06 > 99%
Error	8	0.00	0.00	

Total Comparison

Treatment	Total Comparison				F	Source of Var.	Total Comparison				
	98	99	100	101 Total			98	99	100	101 Total	
	99.03	98.41	97.59	98.54			98.78	97.90	97.18	97.97	
	98.96	98.44	97.11	98.64			98.78	97.91	96.85	97.55	
	99.07	98.59	97.39	98.98			98.86	98.21	97.33	98.25	
Sum Xij	297.06	295.44	292.39	296.16	296.16	1180.75	Sum Xij	296.42	294.02	291.36	293.77
Sum (Xij)^2	29414.89	29094.95	28438.97	29237.02	116185.83	Sum (Xij)^2	29288.28	28815.98	28297.00	28767.19	115168.45
CTj	29414.88	29094.93	28438.86	29236.92	116185.58	CTj	29288.27	28815.92	28296.88	28766.94	115168.01
Sum Sqj	0.006	0.019	0.116	0.106	0.247	Sum Sqj	0.004	0.062	0.121	0.248	0.435
Sum Sq j/n-1	0.003	0.009	0.058	0.053		Sum Sq j/n-1	0.002	0.031	0.060	0.124	
s	0.056	0.096	0.241	0.231		s	0.046	0.176	0.246	0.352	
Mean	99.02	98.48	97.36	98.72		Mean	98.81	98.01	97.12	97.92	
CT	116180.88					CT	115163.74				
Source of Var.	df	Sum Sqs	Mean Sq.	F		Source of Var.	df	Sum Sqs	Mean Sq.	F	
Total	11	4.95				Total	11	4.71			
Treat.	3	4.70	1.57	50.68 >99%		Treat.	3	4.28	1.43	26.21 >99%	
Error	8	0.25	0.03			Error	8	0.44	0.05		

TABLE 16 ANALYSIS OF VARIANCE FOR MgO and Total Major Oxides

GLASS: E-51768-98		SRS Specification		Avg. CELS		Avg. MAL		SRL-ADS		Stand. Dev.	
OXIDE		Min. Wt%	Max. Wt%	Wt%		Wt%		Wt%		Wt%	
SiO ₂	76.0	76.0	78.0	76.76		76.61		77.08		0.240	
Na ₂ O	5.5	5.5	6.5	5.90		5.83		5.78		0.060	
Li ₂ O	6.5	6.5	7.5	6.68		6.66		6.70		0.019	
MgO	1.75	1.75	2.25	2.13		2.13		2.11		0.011	
B ₂ O ₃	7.5	7.5	8.5	7.55		7.57		7.68		0.069	
TOTAL	97.75	100		99.02		98.80		99.35		0.275	
Undesirables		2.25		0.98		1.20		0.65		0.275	
ZrO ₂								0.03			
Al ₂ O ₃			1.89	0.24		0.21		0.20		0.021	
Fe ₂ O ₃			0.29					0.03			
MnO ₂			0.32								
Cr ₂ O ₃			0.15								
NO			0.25								
PbO			0.11					0.01		0.004	
TiO ₂			0.25	0.10				0.09			
F			0.05								
Cl			0.05								
K ₂ O				0.12		0.12		0.12		0.002	
CaO				0.13		0.13		0.16		0.019	
BaO								0.03			
Sb ₂ O ₃											
Total Undesir.				0.589		0.455		0.67		0.109	

TABLE 17. COMPARISON OF THREE LABORATORY ANALYSES E-51768-98

GLASS: E-51768-99									
SRS Specification				Avg. CELS		Avg. MAL		Avg. SRL-ADS	
	Min. Wt%		Max. Wt%	Wt%		Wt%		Wt%	
OXIDE									
SiO2	76.0		78.0	76.30		75.96		76.63	0.335
Na2O	5.5		6.5	5.97		5.86		5.68	0.146
Li2O	6.5		7.5	6.48		6.41		6.51	0.051
MgO	1.75		2.25	1.96		1.94		1.99	0.025
B2O3	7.5		8.5	7.77		7.83		7.92	0.075
TOTAL	97.75		100	98.48		98.00		98.73	0.371
Undesirables			2.25	1.52		2.00		1.27	0.371
ZrO2			1.89	0.31		0.28		0.04	0.021
Al2O3			0.29					0.27	
Fe2O3			0.32					0.03	
MnO2			0.15						
Cr2O3			0.25						
NiO			0.11					0.01	
PbO			0.25	0.31				0.30	0.007
TiO2			0.05						
F			0.05						
Cl				0.36		0.34		0.35	0.010
K2O				0.24		0.22		0.28	0.031
CaO								0.04	
BaO									
Sb2O3				1.22		0.84		1.32	0.253
Total:									

TABLE 18. COMPARISON OF THREE LABORATORY ANALYSES E-51768-99

33-

GLASS: E-51768-100									
SRS Specification		Avg. CELS		Avg. MAL		Avg. SRL-ADS		Stand. Dev.	
OXIDE	Min. Wt%	Max. Wt%	Wt%	Wt%	Wt%	Wt%	Wt%	Wt%	Wt%
SiO2	76.0	78.0	75.63	75.63	76.59	0.553			
Na2O	5.5	6.5	5.86	5.73	5.70	0.085			
Li2O	6.5	7.5	6.29	6.21	6.38	0.087			
MgO	1.75	2.25	1.62	1.60	1.66	0.030			
B2O3	7.5	8.5	7.95	7.95	8.01	0.033			
TOTAL	97.75	100	97.36	97.12	98.34	0.646			
Undesirables		2.25	2.64	2.88	1.66	0.646			
ZrO2					0.08				
Al2O3		1.89	0.46	0.44	0.23				0.128
Fe2O3		0.29			0.03				
MnO2		0.32							
Cr2O3		0.15							
NiO		0.25							
PbO		0.11			0.01				
TiO2		0.25	0.47		0.41				0.042
F		0.05							
Cl		0.05							
K2O			0.55	0.54	0.55				0.005
CaO			0.40	0.40	0.36				0.022
BaO					0.05				
Sb2O3			1.88	1.375	1.72				0.258
Total:									

TABLE 19. COMPARISON OF THREE LABORATORY ANALYSES E-51768-100

GLASS: E-51768-101						
SRS Specification			Avg. CELS		Avg. MAL	
OXIDE	Min. Wt%	Max. Wt%	Wt%	Wt%	Wt%	Vendor Wt%
SiO2	76.0	78.0	76.57	75.82	76.6	76.0
Na2O	5.5	6.5	5.88	5.79	5.9	5.8
Li2O	6.5	7.5	6.64	6.61	6.7	7.2
MgO	1.75	2.25	2.03	2.01	2.0	1.9
B2O3	7.5	8.5	7.60	7.70	7.7	7.8
TOTAL	97.75	100	98.72	97.92	98.90	98.7
Undesirables		2.25	1.28	2.08	1.10	1.30
ZrO2					0.02	
Al2O3		1.89	0.41	0.34	0.40	0.81
Fe2O3		0.29			0.03	0.04
MnO2		0.32			<.01	<.01
Cr2O3		0.15			<.01	<.01
NiO		0.25			<.01	<.01
PbO		0.11			0.01	0.01
TiO2		0.25	0.11		0.11	0.13
F		0.05			0.03	0.05
Cl		0.05			0.01	0.00
K2O			0.19	0.18	0.19	0.19
CaO			0.11	0.11	0.12	0.13
BaO					0.05	
Sb2O3						
Total:			0.82	0.633	<.1	1.42

* Reference: WSRC-RP-90-1219

TABLE 20. COMPARISON OF THREE LABORATORY ANALYSES E-51768-101

APPENDIX A

IDENTIFICATION OF IDMS FRIT SAMPLES

E-51768-2-1	Frit 202, SG-562, QUC-9942 Mfg. 1 July-88, -80+200 Mesh Ferro Corp. AX 845144-2, #3 NH
E-51768-2-2	Frit 202, SG-562, QUC-9940 Mfg. 30 June-88, -80+200 Mesh Ferro Corp. AX845144-2, #2NH
E-51768-2-3	Frit 202, SG-562, QUC-9944 Mfg. 5 July-88, -80+200 Mesh Ferro Corp. AX 845144-3 #4

Samples obtained from tops of bins and numbered 4-17-89.

ACTUAL MONARCH ANALYSIS - SRL FRIT 202

MONARCH ANALYSIS GLASS E-51768-98						MONARCH ANALYSIS GLASS E-51768-99					
DATE:	5/3/90	7/18/90	8/31/90	8/31/90	8/31/90	DATE:	5/3/90	7/18/90	8/31/90	8/31/90	8/31/90
SAMPLE:	98#1598#15	98#2398#23	98#6	98#6	98#6	SAMPLE:	98#2098#20	98#1298#12	98#6	98#6	98#6
OXIDE						OXIDE					
K2O		0.12	0.12	0.12	0.12	K2O		0.34	0.34	0.35	0.35
Li2O	6.72	6.51	6.46	6.92	6.66	Li2O	6.44	6.21	6.17	6.58	6.61
Na2O	5.95	5.72	5.76	5.85	5.81	Na2O	5.81	5.83	5.77	5.91	5.92
Al2O3	0.19	0.22	0.23	0.22	0.23	Al2O3	0.27	0.28	0.27	0.30	0.28
B2O3	7.46	7.87	7.87	7.39	7.43	B2O3	7.71	8.04	8.01	7.73	7.84
CaO		0.12	0.12	0.13	0.13	CaO		0.22	0.22	0.22	0.23
MgO	2.07	2.13	2.11	2.21	2.19	MgO	1.89	1.93	1.94	1.99	1.99
SiO2	76.63	76.63	76.51	76.62	76.64	SiO2	75.95	75.9	76.02	75.96	75.88
Total	99.02	99.32	99.18	99.46	99.21		98.07	98.26	98.75	98.74	99.10

MONARCH ANALYSIS GLASS E-51768-100						MONARCH ANALYSIS GLASS E-51768-101					
DATE:	5/3/90	7/18/90	8/31/90	8/31/90	8/31/90	DATE:	5/3/90	7/18/90	8/31/90	8/31/90	8/31/90
SAMPLE:	100#2000#20	100#6100#6	100#22100#22	100#22100#22	100#22100#22	SAMPLE:	101#15101#15	101#2201#22	101#14	101#14	101#14
OXIDE						OXIDE					
K2O		0.54	0.54	0.54	0.54	K2O		0.18	0.18	0.18	0.18
Li2O	6.24	6.06	5.87	6.34	6.47	Li2O	6.59	6.36	6.42	6.89	6.77
Na2O	5.73	5.72	5.55	5.74	5.84	Na2O	5.76	5.73	5.78	5.81	5.85
Al2O3	0.43	0.45	0.43	0.44	0.43	Al2O3	0.34	0.33	0.34	0.35	0.35
B2O3	7.96	8.12	8.14	7.62	7.75	B2O3	7.64	7.86	7.92	7.57	7.55
CaO		0.39	0.39	0.40	0.40	CaO		0.10	0.11	0.12	0.12
MgO	1.56	1.56	1.60	1.65	1.68	MgO	1.95	2.01	2.04	2.08	2.06
SiO2	75.71	75.52	75.56	75.71	75.70	SiO2	76.02	75.44	75.54	76.01	75.92
Total	97.63	98.36	98.08	98.44	98.81		98.30	98.30	98.33	99.01	98.80

ADS ANALYSIS REFERENCE STANDARD E-51768-101

E-51768	101#7	101#10	101#11	101#12	101#16	101#18	101#20	101#23	AVG.	S.D.
Code:	40412	413	414	415	416	417	418	419		
Time:	17:58	18:02	18:05	18:09	18:12	18:15	18:18	18:21		
Date:	4/17/90	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr		
Ca	0.000	-	-	-	-	-	-	0.023		
Cd	<.001	-	-	-	-	-	-	-		
Co	<.004	-	-	-	-	-	-	-		
Cu	<.001	-	-	-	-	-	-	-		
Mg	1.071	1.107	1.047	1.079	1.120	1.036	1.110	1.117	1.086	0.035
Mn	<.000	-	-	-	-	-	-	-		
Pb	<.020	<.019	<.020	<.019	<.020	-	-	-		
Zn	0.086	0.090	0.092	0.095	0.098	0.232	0.086	0.087	0.108	0.053
Al	0.186	0.187	0.142	0.172	0.182	0.158	0.181	0.173	0.173	0.016
Ba	0.022	0.023	0.020	0.020	0.020	0.019	0.025	0.020	0.021	0.002
Fe	<.002	-	-	-	-	-	-	-		
La	<.003	-	-	-	-	-	-	-		
Li	2.926	2.992	2.842	2.875	3.047	2.774	3.012	2.980	2.931	0.102
Mo	<.004	-	-	-	-	-	-	-		
Ni	<.005	-	-	-	-	-	-	-		
Sn	<.007	-	-	-	-	-	-	-		
Sr	0.000	-	-	-	-	-	-	-		
Ti	0.039	0.050	0.044	0.044	0.047	0.048	0.043	0.042	0.045	0.003
V	<.001	-	-	-	-	-	-	-		
B	2.207	2.231	2.109	2.124	2.264	2.082	2.232	2.236	2.186	0.074
Cr	<.004	-	-	-	-	-	-	-		
P	<.010	-	-	-	-	-	-	-		
Si	32.660	33.661	31.631	31.166	33.085	31.477	33.957	33.177	32.602	1.140
Time:	13:49	13:53	13:58	14:09	14:12	14:16	14:19	14:23		
Date:	3-May	3-May	3-May	3-May	3-May	3-May	3-May	3-May		
Na	4.373	4.409	4.461	4.307	4.355	4.458	4.355	4.385	4.388	0.057
Zr	0.022	0.024	0.026	0.018	0.017	0.015	0.015	0.017	0.019	0.004
Cl-ppm										
C-ppm										
K-wt%	0.149	0.148	0.146	0.14	0.143	0.146	0.146	0.146	0.146	0.003
F-ppm										

CORRECTION FACTORS FROM REFERENCE STANDARD FOR ADS ANALYSES.

ELEMENT WEIGHT TO OXIDE WEIGHT CONVERSION										Ref. Std. 202 Frit		E-51768-101				
OXIDE	MOL WT	Norm.	Wt%	Wt.	%	output	Ref.Std.	Corr	Wt%	ELE	ELE	WT	Wt%	input	Wt%	output
SiO2	60.06	76.29	69.707	76.60	6.893					Si		28.09	32.602			
Na2O	61.99	6.47	5.916	5.90	-0.016					Na		22.991	4.388			
Li2O	29.88	6.91	6.310	6.70	0.390					Li		6.94	2.931			
MgO	40.32	1.97	1.800	2.00	0.200					Mg		24.32	1.086			
B2O3	69.64	7.70	7.035	7.70	0.665					B		10.82	2.186			
ZrO2	123.22	0.00	0.026	0.02	-0.006					Zr		91.22	0.019			
Al2O3	101.94	0.36	0.327	0.40	0.073					Al		26.98	0.173			
Fe2O3	159.7	0.00	0.000	0.03	0.030					Fe		55.85	0			
MnO2	86.93	0.00	0.000							Mn		54.94	0			
Cr2O3	152.02	0.00	0.000							Cr		52.01	0			
NiO	74.69	0.00	0.000							Ni		58.71	0			
PbO	223.21	0.00	0.000	0.01	0.010					Pb		207.21	0			
TiO2	79.9	0.08	0.075	0.11	0.035					Ti		47.9	0.045			
F2	38	0.00	0.000							F2		38	0			
Cl2	70.91	0.00	0.000							Cl2		70.91	0			
ZrO	81.38	0.00	0.000							Zn		65.38	0			
CaO	56.08	0.00	0.000	0.12	0.120					Ca		40.08	0			
P2O5	141.96	0.00	0.000							P		30.975	0			
K2O	94.19	0.19	0.176	0.19	0.014					K		39.1	0.146			
BaO	153.36	0.03	0.023	0.04	0.017					Ba		137.36	0.021			
TOTAL		100.00	91.371	99.82												

.. AA

ADS ANALYSIS SRL FRIT - 202 E-51768-98

E-51768	-98#8	-98#11	-98#12	-98#13	-98#16	98#20	98#22	98#25	AVG.	S.D.
Code:	40388	389	390	391	392	393	394	395		
Time:	9:50	9:53	9:57	10:00	10:04	10:07	10:12	10:15		
Date:	4/17/90	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr		
Ca	0.029	-	0.011	-	-	-	0.029	0.051	0.030	0.020
Cd	<.001	-	-	-	-	-	-	-		
Co	<.004	-	-	-	-	-	-	-		
Cu	<.001	-	-	-	-	-	-	-		
Mg	1.203	1.196	1.200	1.215	1.183	1.040	1.188	1.189	1.177	0.060
Mn	0.006	-	-	-	-	-	-	-		
Pb	<.020	-	-	-	-	-	-	-		
Zn	0.106	0.104	0.090	0.095	0.105	0.099	0.086	0.096	0.098	0.007
Al	0.092	0.092	0.072	0.065	0.050	0.057	0.068	0.079	0.072	0.014
Ba	0.011	0.013	0.012	0.011	0.010	0.009	0.011	0.014	0.011	0.002
Fe	<.002	-	-	-	-	-	-	-		
La	<.003	-	-	-	-	-	-	-		
Li	3.099	3.053	3.038	3.070	2.996	2.679	2.994	3.055	2.998	0.137
Mo	<.004	-	-	-	-	-	-	-		
Ni	<.005	-	-	-	-	-	-	-		
Sn	<.007	-	-	-	-	-	-	-		
Sr	0.000	-	-	-	-	-	-	-		
Ti	0.044	0.045	0.004	0.044	0.040	0.035	0.040	0.043	0.037	0.014
V	<.001	-	-	-	-	-	-	-		
B	2.323	2.273	2.254	2.296	2.216	1.986	2.223	2.288	2.232	0.107
Cr	<.004	-	-	-	-	-	-	-		
P	<.010	-	-	-	-	-	-	-		
Si	34.784	34.322	33.904	34.470	33.645	29.799	33.846	34.026	33.599	1.626
Time:	14:35	14:39	14:42	14:46	14:50	14:53	14:56	15:00		
Date:	1-May	1-May	1-May	1-May	1-May	1-May	1-May	1-May		
Na	4.137	4.260	4.339	4.347	4.459	4.530	4.592	4.478	4.393	0.118
Zr	0.048	0.026	0.023	0.029	0.023	0.023	0.026	0.020	0.027	0.003
Cl-ppm										
C-ppm										
K-wt%	0.084	0.086	0.088	0.084	0.088	0.088	0.083	0.093	0.087	0.003
F-ppm										

ADS CORRECTED/NORMALIZED ANALYSIS E-51768-98

E-51768-98 Avg/ of 8

ELEMENT WEIGHT TO OXIDE WEIGHT CONVERSION												
OXIDE	MOL WT	Wt. % output	Corr F	Corr. Wt%	Norm.	100%	ELE	ELE WT	Wt%	Input	Wt. %	output
SiO2	60.06	71.839	6.893	78.73		77.08	Si	28.09	33.599	33.599	0.000	0.000
Na2O	61.99	5.922	-0.016	5.91		5.78	Na	22.991	4.393	4.393	0.000	0.000
Li2O	29.88	6.454	0.390	6.84		6.70	Li	6.94	2.998	2.998	0.000	0.000
MgO	40.32	1.951	0.200	2.15		2.11	Mg	24.32	1.177	1.177	0.000	0.000
B2O3	69.64	7.183	0.665	7.85		7.68	B	10.82	2.232	2.232	0.000	0.000
ZrO2	123.22	0.036	-0.006	0.03		0.03	Zr	91.22	0.027	0.027	0.000	0.000
Al2O3	101.94	0.136	0.073	0.21		0.20	Al	26.98	0.072	0.072	0.000	0.000
Fe2O3	159.7	0.000	0.030	0.03		0.03	Fe	55.85	0	0	0.000	0.000
MnO2	86.93	0.000					Mn	54.94	0	0	0.000	0.000
Cr2O3	152.02	0.000					Cr	52.01	0	0	0.000	0.000
NiO	74.69	0.000					Ni	58.71	0	0	0.000	0.000
PbO	223.21	0.000	0.010	0.01		0.01	Pb	207.21	0	0	0.000	0.000
TiO2	79.9	0.062	0.035	0.10		0.09	Ti	47.9	0.037	0.037	0.000	0.000
F2	38	0.000					F2	38	0	0	0.000	0.000
Cl2	70.91	0.000					Cl2	70.91	0	0	0.000	0.000
ZnO	81.38	0.000					Zn	65.38	0	0	0.000	0.000
CaO	56.08	0.042	0.120	0.16		0.16	Ca	40.08	0.03	0.03	0.000	0.000
P2O5	141.96	0.000					P	30.975	0	0	0.000	0.000
K2O	94.19	0.105	0.014	0.12		0.12	K	39.1	0.087	0.087	0.000	0.000
BaO	153.36	0.012	0.017	0.03		0.03	Ba	137.36	0.011	0.011	0.000	0.000
TOTAL		93.730		102.138		100.000						

From Atomic Absorbtion

ADS ANALYSIS SRL FRIT 202, E-51768-99

E-51768	-99#7	-99#8	-99#11	-99#15	-99#16	99#17	99#22	99#23	AVG.	S.D.
Code:	40396	397	398	399	400	401	402	403		
Time:	10:23	10:26	10:30	10:33	10:36	10:40	10:43	10:46		
Date:	4/17/90	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr		
Ca	0.084	0.191	0.106	0.077	0.132	0.183	0.105	0.064	0.118	0.049
Cd	0.001	-	-	-	-	-	-	-		
Co	<.004	<.004	-	-	-	-	-	-		
Cu	<.001	-	-	-	-	-	-	-		
Mg	1.120	1.146	1.133	1.094	1.193	1.116	1.081	1.094	1.122	0.039
Mn	0.012	<0.000	0.015	-	-	-	-	-		
Pb	<.020	-	-	-	-	-	-	-		
Zn	0.104	0.107	0.109	0.105	0.097	0.108	0.106	0.114	0.106	0.005
Al	0.138	0.154	0.131	0.103	0.087	0.113	0.088	0.062	0.110	0.031
Ba	0.020	0.021	0.020	0.018	0.019	0.016	0.015	0.014	0.018	0.003
Fe	<.002	0.135	0.042	<.002	-	0.066	-	-		
La	<.003	-	-	-	-	-	-	-		
Li	2.932	2.969	2.962	2.937	3.073	2.947	2.843	2.911	2.947	0.069
Mo	<.004	-	-	-	-	-	-	-		
Ni	<.005	-	-	-	-	-	-	-		
Sn	<.007	-	-	-	-	-	-	-		
Sr	0.001	0.002	-	-	-	-	-	-		
Ti	0.163	0.177	0.161	0.167	0.158	0.158	0.152	0.156	0.162	0.008
V	<.001	-	-	-	-	-	-	-		
B	2.325	2.350	2.357	2.335	2.433	2.342	2.257	2.302	2.338	0.054
Cr	<.004	-	-	-	-	-	-	-		
P	<.010	-	-	-	-	-	-	-		
Si	33.870	34.088	33.986	33.844	35.564	33.005	32.810	33.651	33.852	0.899
Time:	15:07	15:10	15:13	15:16	15:19	15:23	15:27	15:31		
Date:	1-May	1-May	1-May	1-May	1-May	1-May	1-May	1-May		
Na	4.437	4.171	4.441	4.761	4.218	4.409	4.458	4.083	4.372	0.228
Zr	0.045	0.036	0.032	0.037	0.030	0.034	0.035	0.035	0.036	0.002
Cl-ppm										
C-ppm										
K-wt%	0.286	0.294	0.29	0.312	0.27	0.291	0.293	0.267	0.288	0.015
F-ppm										

ADS CORRECTED/NORMALIZED ANALYSIS E-51768-99

E-51768-99									
ELEMENT WEIGHT TO OXIDE WEIGHT CONVERSION									
OXIDE	MOL WT	Wt % Input	Wt % output	Corr F	Corr F	Corr. Wt%	Norm.	100%	ELE
SiO2	60.06		72.380	6.893		79.27		76.63	Si
Na2O	61.99		5.894	-0.016		5.88		5.68	Na
Li2O	29.88		6.344	0.390		6.73		6.51	Li
MgO	40.32		1.860	0.200		2.06		1.99	Mg
B2O3	69.64		7.524	0.665		8.19		7.92	B
ZrO2	123.22		0.049	-0.006		0.04		0.04	Zr
Al2O3	101.94		0.208	0.073		0.28		0.27	Al
Fe2O3	159.7		0.000	0.030		0.03		0.03	Fe
MnO2	86.93		0.000						Mn
Cr2O3	152.02		0.000						Cr
NiO	74.69		0.000						Ni
PbO	223.21		0.000	0.010		0.01		0.01	Pb
TiO2	79.9		0.270	0.035		0.31		0.30	Ti
F2	38		0.000						F2
Cl2	70.91		0.000						Cl2
ZrO	81.38		0.000						Zn
CaO	56.08		0.165	0.120		0.29		0.28	Ca
P2O5	141.96		0.000						P
K2O	94.19		0.347	0.014		0.36		0.35	K
BaO	153.36		0.020	0.017		0.04		0.04	Ba
TOTAL			95.041			103.449		100.000	

• • From Atomic absorption

443

- 43 -

ADS ANALYSIS SRL FRIT 202, E-51768-100

E-51768	100#8	100#11	100#13	100#14	100#17	100#19	100#23	0.489	AVG.	S.D.
Code:	40404	405	406	407	408	409	410	411		
Time:	17:30	17:33	17:39	17:42	17:45	17:48	17:52	17:55		
Date:	4/17/90	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr	17-Apr		
Ca	0.185	0.187	0.162	0.180	0.201	0.181	0.169	0.171	0.180	0.013
Cd	<.001	-	-	-	-	-	-	-		
Co	<.004	<.004	-	-	-	-	-	-		
Cu	<.001	-	-	-	-	-	-	-		
Mg	0.884	0.929	0.937	0.888	0.881	0.895	0.910	0.885	0.901	0.022
Mn	<.000	-	-	-	-	-	-	-		
Pb	<.020	<.019	-	-	-	-	-	-		
Zn	0.143	0.150	0.160	0.142	0.150	0.139	0.143	0.146	0.147	0.007
Al	0.084	0.101	0.109	0.096	0.080	0.073	0.070	0.053	0.083	0.020
Ba	0.029	0.028	0.026	0.026	0.026	0.027	0.025	0.025	0.027	0.001
Fe	0.005	<.002	-	-	-	0.066	-	-		
La	<.003	-	-	-	-	-	-	-		
Li	2.844	2.930	2.882	2.810	2.840	2.820	2.837	2.775	2.842	0.051
Mo	<.004	-	-	-	-	-	-	-		
Ni	<.005	-	-	-	-	-	-	-		
Sn	<.007	-	-	-	-	-	-	-		
Sr	0.000	-	-	-	-	-	-	-		
Ti	0.232	0.234	0.237	0.219	0.222	0.223	0.232	0.223	0.228	0.007
V	<.001	-	-	-	-	-	-	-		
B	2.360	2.417	2.377	2.294	2.325	2.306	2.323	2.263	2.333	0.052
Cr	<.004	-	-	-	-	-	-	-		
P	<.010	-	-	-	-	-	-	-		
Si	33.617	34.685	34.498	33.253	33.414	31.975	32.513	32.846	33.350	0.996
Time:	12:56	12:59	13:02	13:06	13:13	13:24	13:34	13:44		
Date:	3-May	3-May	3-May	3-May	3-May	3-May	3-May	3-May		
Na	4.537	4.394	3.940	4.459	4.176	4.367	4.168	4.591	4.329	0.218
Zr	0.075	0.066	0.060	0.064	0.058	0.072	0.065	0.069	0.066	0.005
Cl-ppm										
C-ppm										
K-wt%	0.467	0.456	0.424	0.472	0.449	0.448	0.435	0.489	0.455	0.022
F-ppm										

-44-

E-51768-100													ADS Avg 8	
ELEMENT WEIGHT TO OXIDE WEIGHT CONVERSION														
OXIDE	MOL WT	Wt %	Wt %	output	Corr F	Corr. Wt %	Norm. 100%	ELE	ELE WT	Wt %	Input	Wt %	output	
SiO2	60.06			71.307	6.89	78.20	78.59	Si	28.09		33.350		0.000	
Na2O	61.99			5.836	-0.02	5.82	5.70	Na	22.991		4.329		0.000	
Li2O	29.88			6.118	0.39	6.51	6.37	Li	6.94		2.842		0.000	
MgO	40.32			1.494	0.20	1.69	1.66	Mg	24.32		0.901		0.000	
B2O3	69.64			7.508	0.67	8.17	8.00	B	10.82		2.333		0.000	
ZrO2	123.22			0.089	-0.01	0.08	0.08	Zr	91.22		0.066		0.000	
Al2O3	101.94			0.157	0.07	0.23	0.23	Al	26.98		0.083		0.000	
Fe2O3	159.7			0.000	0.03	0.03	0.03	Fe	55.85		0		0.000	
MnO2	86.93			0.000				Mn	54.94		0		0.000	
Cr2O3	152.02			0.000				Cr	52.01		0		0.000	
NiO	74.69			0.000				Ni	58.71		0		0.000	
PbO	223.21			0.000	0.01	0.01	0.01	Pb	207.21		0		0.000	
TiO2	79.9			0.380	0.04	0.42	0.41	Ti	47.9		0.228		0.000	
F2	38			0.000				F2	38		0		0.000	
Cl2	70.91			0.000				Cl2	70.91		0		0.000	
ZnO	81.38			0.000				Zn	65.38		0		0.000	
CaO	56.08			0.252	0.12	0.37	0.36	Ca	40.08		0.180		0.000	
P2O5	141.96			0.000				P	30.975		0		0.000	
K2O	94.19			0.548	0.01	0.56	0.55	K	39.1		0.455		0.000	
BaO	153.36			0.030	0.02	0.05	0.05	Ba	137.36		0.027		0.000	
TOTAL				93.689		102.097	100.000							

.. From AA

END

DATE
FILMED

4 / 3 / 93