Final Report

**DOE/PC/89796-7
(DE92006876)**

**STORAGE, TRANSPORTATION, AND ATOMIZATION OF CWF FOR RESIDENTIAL
APPLICATIONS**

Final Report for the Period September 27, 1989–November 15, 1991

**By
M. P. Grimanis
R. W. Breault
F. J. Smit
Mahesh C. Jha**

November 1991

Work Performed Under Contract No. AC22-89PC89796

**For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

**By
Tecogen Inc.
Waltham, Massachusetts**

and

**AMAX R&D Center
Golden, Colorado**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**STORAGE, TRANSPORTATION, AND ATOMIZATION
OF CWF FOR RESIDENTIAL APPLICATIONS**

Final Report

November 1991

**Work Performed Under Contract DE-AC22-89PC89796
September 27, 1989 to November 15, 1991**

**Prepared for
PETC Project Manager: Anthony Mayne
Pittsburgh Energy Technology Center
U.S. Department of Energy
P.O. Box 10940
Pittsburgh, Pennsylvania 15236-0940**

**Prepared by
M.P. Grimanis and R.W. Breault
Tecogen Inc.
45 First Avenue
P.O. Box 9046
Waltham, Massachusetts 02254-9046**

and

**F.J. Smit and M.C. Jha
AMAX R&D Center
5950 McIntyre Street
Golden, Colorado 80403-7499**

TABLE OF CONTENTS

EXECUTIVE SUMMARY	1
1. INTRODUCTION	2
2. LITERATURE REVIEW	4
2.1 EFFECTS OF BENEFICIATION ON THE CHEMISTRY, RHEOLOGY, AND STABILITY OF CWFs	5
2.1.1 Chemistry	5
2.1.2 Rheology	6
2.1.3 Stability	12
2.2 FUEL MANUFACTURING	17
2.2.1 CWF Specifications	17
2.2.2 Feedstock Selection	18
2.2.3 Manufacturing Coal-Water Fuel (CWF)	18
2.3 HANDLING AND TRANSPORTATION STUDIES OF CWFs BY PERFORMING ORGANIZATIONS	20
2.3.1 TRW Space and Technology Group	20
2.3.2 Atlantic Research Corporation	22
2.3.3 Electric Power Development Company (Japan)	24
2.3.4 Bechtel Power Corporation	25
2.3.5 EPRI/Du Pont/Babcock & Wilcox	26
2.3.6 Valleydale Packers	27
2.3.7 Adelphi University	27
2.3.8 DOE/University of Pittsburgh	27
2.3.9 Universite de Technologie de Compiègne/Elf Aquitaine ...	28
2.3.10 Combustion Engineering/OXCE Fuels	28
2.3.11 AMAX R&D Experience	28
3. FUEL PREPARATION	30
3.1 NOMINAL FUEL SPECIFICATIONS	30
3.2 BENEFICIATION PROCESSES	30
3.2.1 Heavy Media Separation	35
3.2.2 Chemical Cleaning	35
3.2.3 Froth Flotation	35
3.2.4 Oil Agglomeration	39
3.3 CWF CHARACTERISTICS AND PROPERTIES	39
4. BULK STORAGE	46
4.1 CHEMICAL STABILIZATION	46
4.2 MECHANICAL RESUSPENSION	56
4.2.1 Periodic Agitation	56
4.2.2 Storage Tank Configuration	58
4.2.3 Recycling Pumping Strategy	65

TABLE OF CONTENTS (Continued)

5. RESIDENTIAL STORAGE	67
5.1 TANK DESIGN	67
5.2 STORAGE AND HANDLING SYSTEM	70
5.3 CLIMATIC ASSESSMENT	73
6. RESIDENTIAL HANDLING (TASK 5)	75
6.1 PUMP EVALUATION	75
6.2 TRANSFER LINE EVALUATION	76
6.3 CAPILLARY VISCOMETRY	87
7. ATOMIZATION	94
8. ECONOMIC EVALUATION	118
9. CONCLUSIONS AND RECOMMENDATIONS	123
REFERENCES	125
 APPENDIX A: DATA ON PERIODIC REMIXING ON STABILITY	 129
APPENDIX B: PLOTS OF HARD-PACK DEPTHS FOR VARIOUS REMXING FREQUENCIES	 138

LIST OF ILLUSTRATIONS

2.1	Viscosity as a Function of Shear for a Typical CWF	10
3.1	No Cleaning or HMS Cleaning	36
3.2	Chemical Cleaning	37
3.3	Froth Flotation Cleaning	38
3.4	Oil Agglomeration	40
4.1	Stabilizer Required to Provide 2-Month Stabilization for All Coals .	50
4.2	Stabilizer Required to Provide 2-Month Stabilization by Source Coal	50
4.3	Stabilizer Required to Provide 2-Month Stabilization by Beneficiation Process	50
4.4	Stabilizer Required to Provide 2-Month Stabilization versus the Rosin-Rammler Slope Parameter by MMD	50
4.5	Stabilizer Required to Provide 2-Month Stabilization versus the Rosin-Rammler Slope Parameter by Source Coal	51
4.6	Stabilizer Required to Provide 2-Month Stabilization versus Weight Fraction in Mid-Range by MMD	51
4.7	Stabilizer Required to Provide 2-Month Stabilization versus Weight Fraction in Mid-Range by Source Coal	51
4.8	Stabilizer Required to Provide 2-Month Stabilization versus Calculated Specific Surface by MMD	51
4.9	Stabilizer Required to Provide 2-Month Stabilization versus Calculated Specific Surface by Source Coal	52
4.10	Stabilizer Required to Provide 2-Month Stabilization versus Weight Percent Under 2 μ m by MMD	52
4.11	Stabilizer Required to Provide 2-Month Stabilization versus Weight Percent Under 2 μ m by Source Coal	52
4.12	Regression Analysis of Stabilizer Required to Obtain 2-Month Stability	55
4.13	Sediment Accumulated in Slurries Prepared from Beneficiated Upper Elkhorn Coal After 2 Months of a Weekly Remixing Schedule	59

LIST OF ILLUSTRATIONS (Continued)

4.14	Average Viscosities of Four Sample Slurries Which Did Not Contain Flocon	61
4.15	Average Viscosities of Four Samples Which Did Contain Flocon ..	61
5.1	Ultrasonic Sensor Results	69
5.2	Photograph of Storage and Handling System	71
5.3	Residential Slurry Storage and Handling System	72
6.1	Volumetric Flow Rate of Two Slurries versus Setting on the Peristaltic Pump Used in the Transfer Line Evaluation	77
6.2	Illinois No. 6 - Heavy Media Separated	79
6.3	Wyodak - HMS	80
6.4	Upper Elkhorn HMS	81
6.5	Upper Elkhorn HMS, Filtered and Washed	82
6.6	Upper Elkhorn - Chemically Cleaned	83
6.7	Upper Elkhorn No. 3 - Froth Flotation	84
6.8	Illinois No. 6 - Oil Agglomeration	85
6.9	Investigation of Alternate Materials	86
6.10	Batch A - Pressure Drop versus Flow Rate	88
6.11	Batch C - Pressure Drop versus Flow Rate	89
6.12	Batch D - Pressure Drop versus Flow Rate	90
6.13	Batch E - Pressure Drop versus Flow Rate	91
6.14	Capillary Viscometer Setup	92
7.1	Schematic of Experimental Configuration	95
7.2	Cutaway Drawing of Tecogen's CWF Fuel Atomizer	97
7.3	Delavan-Delta Nozzle	98
7.4	Cutaway of Bete's XA-EF Series	99
7.5	Tecogen Nozzle - Water	101

LIST OF ILLUSTRATIONS (Continued)

7.6	Tecogen Nozzle - Illinois No. 6 - HMS	102
7.7	Tecogen Nozzle - Wyodak	103
7.8	Tecogen Nozzle - Upper Elkhorn - HMS	104
7.9	Tecogen Nozzle - Upper Elkhorn - HMS/Filtered	105
7.10	Tecogen Nozzle - Upper Elkhorn - HMS	106
7.11	Tecogen Nozzle - Upper Elkhorn - HMS	107
7.12	Tecogen Nozzle - Upper Elkhorn - HMS	108
7.13	Tecogen Nozzle - Upper Elkhorn - HMS	109
7.14	Tecogen Nozzle - Upper Elkhorn - HMS	110
7.15	Tecogen Nozzle - Upper Elkhorn - HMS	111
7.16	Delavan Nozzle - Upper Elkhorn - HMS	112
7.17	Delavan Nozzle - Upper Elkhorn - HMS	113
7.18	Bete Nozzle - Upper Elkhorn - HMS	114
7.19	Bete Nozzle - Upper Elkhorn - HMS	115
7.20	Droplet Size Distribution of Water from Nozzle A	117
8.1	Assembly Drawing of Manufacturing Prototype Furnace	119
8.2	Residential Slurry Storage and Handling System	120
8.3	Economic Comparison	122

LIST OF TABLES

2.1	Typical Additive-Related CWF Parameters	7
2.2	Typical Coal Beneficiation Effects	8
3.1	Source Coals	31
3.2	Representative Analysis of As-Received Parent Coals	32
3.3	Nominal Fuel Specifications	33
3.4	Cleaning Process and Source Coal Matrix	34
3.5	Properties of Coal Water Fuels	41
3.6	Heating Values of Coal Water Fuels	42
3.7	Significant Physical Properties of Beneficiated Coals	43
3.8	Concentration of Common Elements in Aqueous Phase of Coal Slurry Fuels Prepared From Beneficiated Upper Elkhorn Coal	45
4.1	Stability of Slurries Containing Added Chemical Stabilizer	47
4.2	Stability Rating	48
4.3	Summary of Chemical Stabilization 2-Month Storage Test Results	49
4.4	Viscosities of Selected Slurries After 2 Months of Periodic Remixing	60
4.5	Results of Mixing Tests for Resuspension of Sediment	63
4.6	Summarized Resuspension Test Results	64
7.1	Particle Size Measurements	116

EXECUTIVE SUMMARY

In light of the increased interest to decrease SO_2 emissions, one of the main causes of acid rain, and considering the large market potential for use of coal in residential/small-scale applications, the following program was undertaken. The work investigated the properties and behavior with regard to handling, storage, and atomization in small-scale applications of different CWFs (coal water fuels) prepared from different parent coals and various beneficiation techniques as well as consideration for bulk storage and distribution. The CWFs that were prepared included Upper Elkhorn No. 3, Illinois No. 6, and Upper Wyodak coal cleaned by heavy media separation. Also, several CWFs were prepared with Upper Elkhorn No. 3 coal cleaned by heavy media separation with filtration, chemical cleaning, oil agglomeration, and froth flotation.

Pressure drop measurements in tubes and viscometer measurements were used to construct rheograms of the seven CWFs that were prepared for shear rates up to 150,000 1/s. It was shown that tube material does not have an effect on the friction losses in the tubes. Analysis of each CWF included proximate, ultimate, and ash fusion temperatures. A two-month stability could be obtained with the CWFs. The CWF made with lower ranked coals and with wider particle size distributions required less stabilizer to maintain stability. Different tank configurations and resuspension schemes were investigated for both bulk and small-scale storage. Two externally mixed atomizers were tested, as was one internally mixed atomizer. A fully automatic demonstration storage facility was designed, fabricated, and tested. A cost evaluation of a CWF furnace system showed a typical payback of 10 years.

1. INTRODUCTION

There are continuing pressures in the United States to reduce SO₂ emissions in order to control acid rain and its damage to the environment. Advanced beneficiation processes are under development to provide low-ash, low-sulfur coals to allow combustion performance approximately equal to that of oil or gas. A major benefit of this development will be the contribution of these technologies to the abatement of acid rain precursors.

In addition to the industrial applications of beneficiated coal products, there is a large market potential for use of these fuels in small-scale applications, including small industrial, commercial, and residential combustion systems. However, it is important to transmute this beneficiated fuel into a more acceptable form for the small-scale user; a coal-water fuel (CWF) similar to oil is needed. Although much work has been done on the development of components and systems for the formulation and use of CWF for large industrial and utility applications, the results of these R&D efforts are not directly applicable to smaller combustors. It is essential to develop a data base for future use of CWF for these applications.

Under a contract with the Department of Energy's Pittsburgh Energy Technology Center (PETC), Tecogen Inc., developed a CWF-fired advanced combustor for commercial and residential applications. In order to expeditiously bring the technology to the point of commercial readiness, it is important to develop components and systems for storage, transportation, and handling of these fuels for end use. The work conducted in this program included fuel preparation, bulk storage, residential storage, and handling and atomization. This research and development effort is designed to augment the data base on the use of CWF for residential and other smaller scale applications.

A highly qualified team was assembled to perform the contract. The primary responsibilities of the team members were as follows:

1. Tecogen Inc. is a subsidiary of Thermo Electron Corporation, Waltham, Massachusetts. As the prime contractor, Tecogen managed and directed the program. The CWF storage and handling tests were carried out in their advanced combustor facilities for residential applications.
2. AMAX R&D of Golden, Colorado, assessed formulations of CWF and prepared the fuel from the beneficiated coal products supplied by DOE in order to conduct tests in the program. AMAX R&D focused on bulk storage requirements prior to distribution for regional residential use.

3. Carnegie-Mellon University of Pittsburgh, Pennsylvania, compared the atomization characteristics of the CWFs prepared in the program. The effects of beneficiation on atomization were examined, and spray characteristics were studied by means of high-speed photography and a Malvern Particle Size Analyzer.

The test program examined the stability and rheology of the CWFs prepared from the beneficiated coal products supplied by DOE and made from various coals representing geographical regions in the United States. The following represents the source coals and their rank and origin.

Source Coal	Rank	Location of Mine
Upper Elkhorn No. 3	Bituminous, hvA	Wentz Plant, Virginia
Illinois No. 6	Bituminous, hvC	Marion, Illinois
Upper Wyodak	Subbituminous, Group C	Gillette, Wyoming

The fuel characterization included: particle size distribution, ultimate and proximate analyses of coal, ash composition, ash fusion temperature, and solids concentration. For rheological characteristics, data were obtained at varying shear rates, agitation, or recirculation in the bulk storage tanks. The effect of freeze-thaw on the stability and rheology of the CWF was also evaluated.

The bulk storage studies involved testing CWF stability characteristics with and without agitation or recirculation. Different tank configurations were tested by AMAX R&D. The residential CWF storage and handling tests were carried out in Tecogen's CWF-fired advanced combustor facilities.

Carnegie-Mellon University evaluated the atomization characteristics of the various atomizers as a function of coal type, formulation, and operating conditions.

Tecogen Inc., and its subcontractors were aware of the work previously carried out and currently under way in the formulation of CWF using beneficiated coal products as well as the data available in the public domain. No attempt was made to duplicate the work funded previously by DOE or through other research organizations such as EPRI.

2. LITERATURE REVIEW

The CWF prepared from wet cake or dry ultra-fine beneficiated coals for the residential furnace applications has a 50- to 60-percent solids concentration. Above these levels, the viscosity of the slurry increases sharply with solids concentration. As a result, the additives used for formulation of the CWF should provide fluidity for effective atomization and combustion. At the same time, stability in storage and transportation is essential so that coal particles do not settle down. Other factors affecting the CWF characteristics are type of coal, degree of beneficiation, advanced cleaning processes, coal particle size distribution, and the method of formulating slurries. Also, whereas the objective for extended storage is to achieve stability over a period of several weeks with minimal settling and easy resuspension (or no settling), the slurry stored in the residence should be easily atomized. This literature review provides some insight into the expected behavior of slurries produced from beneficiated coals. The review focuses on the impact beneficiation processes have on chemistry, rheology, stability, handling, environmental effects, transportation, and atomization. In addition, the literature review consists of technology for manufacturing, transportation, and handling micronized CWFs. It provided background information for selecting suitable fuels and highlighted relevant issues to be taken into consideration when planning a bulk distribution system.

This review is based on literature sources and the experience of AMAX R&D and Tecogen. Most of the published information dates from the early to mid-1980s when there was considerable interest in repowering oil-fired utility boilers with coal-slurry fuel. Consequently, the literature citations emphasize boiler-grind (minus 0.3 mm) slurries rather than the micronized grades considered for the Tecogen heating system. Some of the experience gained from these earlier programs was transferred to the design and operation of distribution systems for supplying CWF to residential users.

The following literature review is broken down into several major sections:

- Effects of Beneficiation on the Chemistry, Rheology, and Stability of CWFs
- CWF Manufacturing
- Handling and Transportation Studies of CWFs by Performing Organization

2.1 EFFECTS OF BENEFICIATION ON THE CHEMISTRY, RHEOLOGY, AND STABILITY OF CWFs

This section describes the chemical, rheological, and stabilization parameters considered during the program.

2.1.1 Chemistry

Coal beneficiation has been carried out to reduce sulfur and mineral matter from finely ground parent coal prior to CWF production. The beneficiation of coal results in a reduction of SO_x emissions, total particulate emissions, and waste ash production. Besides these benefits, the beneficiation process results in reduced moisture levels in coal and improved grindability, thereby improving combustion efficiency and reducing grinding costs.

However, the beneficiation processes also affect the physical and chemical characteristics of the beneficiated fuel (BF), thus altering the particle chemistry (especially surface chemistry), particle density, particle shape, and particle homogeneity, depending on the degree of the beneficiation process. Some studies^{1,2,3} have reported that coal beneficiation can result in undesirable CWF rheology and time-dependent slurry deterioration. The interactions of parent coal properties, beneficiation effects, and slurry-additive chemistry are very complex. A thorough understanding of these interactions is needed to formulate CWF with the required stability, rheological behavior, atomization, and combustion characteristics.

The various coal beneficiation processes affect the properties of CWF differently because of contamination by cleaning agents such as those used for flotation and agglomeration, and because of changes in coal particle surface chemistry. These changes affect both the surface charge as well as the wettability of coal.

The magnitude of the coal particle surface charge controls the rheology and sedimentation stability of CWF.^{4,5} When the surface charge is low or zero, particles flocculate, which results in enhanced sedimentation stability and increased viscosity. When surface charge is high, viscosity is low, but sedimentation stability is adversely affected. At intermediate surface charge, an acceptable compromise can be reached between sedimentation stability and moderate viscosity.

A major determinant of coal particle surface charge is the nature and quantity of ash associated with the coal. Because of the presence of clay materials, pyrite, calcium, magnesium compounds, and oxygen-containing functional groups

in the parent coal, the pH dependence of the surface charge may be complex. Removal of ash by beneficiation leads to a less heterogeneous surface and a simpler, possibly more predictable, pH dependence of charge as the surface chemistry becomes more carbonaceous.

A second determinant of surface charge is the degree of wetting of the coal particles. Only wetted regions of the surface contribute to surface charge in a CWF. Although there is no simple parameter that might be measured to predict the degree, or even the direction, of changes in CWF characteristics that would result from beneficiation of coal, tests carried out with four bituminous coals at Carnegie-Mellon University suggest the possibility that higher ash coals are more easily wetted than others and have higher critical surface tensions for wetting. It appears that the clay minerals or other ash components have a greater affinity for water than other regions of the surface.

In limited tests carried out,⁶ comparison of the microelectrophoretic mobility of dilute suspensions of three different bituminous coals in slurry liquor indicated that the particle surface becomes more strongly negative after the removal of ash. The additive formulation for the CWF following the beneficiation may, therefore, result in the use of more expensive nonionic dispersants. Coal surfaces can be rendered more hydrophobic during beneficiation because of contamination of the surface by hydrophobic cleaning agents. Thus, less expensive anionic dispersants such as ammonium lignosulfonates cannot be used as dispersants.

The adverse impact of this limitation on dispersant type due to hydrophobic coal cleaning is not limited to the higher additive cost of nonionic dispersant. Subsequent atomization and combustion behavior may also suffer due to formation of gels.⁶ However, nonionically dispersed CWF typically has low negative zeta potentials compared to anionically dispersed CWF, and is not so adversely impacted by pH drift and increases in multivalent cation concentrations. Tables 2.1 and 2.2 summarize some of the effects of coal beneficiation on CWF formulation and performance.

2.1.2 Rheology

For small-scale applications, such as residential furnaces, serious constraints on fuel formulations are imposed by considerations of fuel storage, transfer requirements, and the suitability of the formulation to advanced combustor concepts. Specific R&D needs for the CWF include investigation of flow behavior through narrow pipes and characterization of rheology of the CWF to determine key factors relating to atomization and combustion.

TABLE 2.1
TYPICAL ADDITIVE-RELATED CWF PARAMETERS

<u>Parameter</u>	<u>Nonionic</u>	<u>Anionic</u>	<u>Additive-Free</u>
Cost	High	Moderate	Low
pH	6.3 – 8.7	7.3 – 8.2	9 – 10
Zeta Potential	–2 mv to –25 mv	–8 mv to –56 mv	–68 mv
Suitability for Hydrophobic Beneficiation	Good	Poor	Very Poor
Effect of pH Drift	Slightly Adverse	Significantly Adverse	Highly Adverse
Effect of Multivalent Cations	Weak	Strong	Very Strong

Adapted from Reference 6.

TABLE 2.2
TYPICAL COAL BENEFICIATION EFFECTS

<u>Effect</u>	<u>Heavy Media</u>	<u>Oil Agglomeration</u>	<u>Froth Flotation</u>	<u>Generic Hydrophilic</u>
Additive Cost	low/moderate	high	high	low/moderate
Chemical Drift Effects	high	low	low	moderate
Atomization	good	fair	fair	good
Combustion	good/excellent	fair	fair	good/excellent
Slagging/Fouling	more severe	variable	variable	variable

Adapted from Reference 6.

CWF rheology is complex and is dependent on composition and formulation. The particle-size distribution, coal type, extent of coal beneficiation, coal loading, and additive package contribute to the rheological characteristics of the CWF. CWF rheology typically exhibits shear-dependent behavior such as pseudoplasticity or dilatancy and can be thixotropic or rheopectic. The wide range of fluid behavior of CWF makes it difficult to use single shear rate viscosity measurements as a basis of comparison. The rheological behavior of CWF is usually depicted as a plot of shear stress (τ) against rate of shear ($\dot{\gamma}$). The shape of this plot generally conforms to one of the following mathematical formulations:

$$\tau = \eta \dot{\gamma} \text{ Newtonian} \quad (1)$$

$$\tau = \kappa \dot{\gamma}^n \quad \begin{array}{l} n < 1 \text{ Pseudoplastic} \\ n > 1 \text{ Dilatant} \end{array} \quad (2)$$

$$\tau = \tau_0 + \eta_{pl} \dot{\gamma} \text{ Plastic/Bingham} \quad (3)$$

$$\tau = \tau_0 + \kappa \dot{\gamma}^n \quad \begin{array}{l} n < 1 \text{ Pseudoplastic with yield valve} \\ n > 1 \text{ Dilatant with yield valve} \end{array} \quad (4)$$

where η is the CWF viscosity, κ is the flow consistency number, n is the flow behavior index, τ_0 is the yield stress, and η_{pl} is the plastic viscosity.

Equation 2 is often referred to as the power law or the Ostwald-de Waele equation, and Equation 4 as the power law with yield, or the Herschel-Buckley equation. The values of τ_0 and η reflect the magnitude of the deviation from Newtonian flow (Equation 1), and are dependent upon the state of dispersion and coal particles.

The rheology of CWF will depend strongly on coal type, extent and method of beneficiation, solids content, particle size distribution, and additives used in the formulation. Initially, the CWFs show a reduction in viscosity with increasing shear rate (as shown in Figure 2.1), the magnitude of which is based on the additive levels and particle size distribution.

After the initial reduction, the viscosity remains constant until the accumulated amount of shear increases to the design point. Once this level of shear is reached, the viscosity of the fuel gradually increases and a yield point forms. This viscosity continues to increase with accumulated shear until the fluid can no longer be pumped. If a sample of this "worked" CWF were tested, it would exhibit a completely different shear stress/shear rate behavior from its original

Figure 2.1 Viscosity as a Function of Shear for a Typical CWF

rheogram. There are many causes for this behavior: comminution, deagglomeration, additive evaporation, or changes in the zeta potential.

The purpose of measuring the rheology of CWF is to obtain information about how the CWF will perform during storage, handling, and atomization leading to combustion. Most CWF viscosity measurements reported in the literature have been made using a Brookfield viscometer or Haake Rotovisco, which provides well-defined shear flows. The maximum shear rates in these instruments vary between 100 and 1000 sec^{-1} . For higher shear rate measurements, capillary rheometry is used, in which shear rates vary from 1,000 to 150,000 sec^{-1} (thus being more representative of the shear rates expected in dual-fluid atomizers). In shear flow, the velocity gradient is perpendicular to the flow direction, and particles or polymer molecules adopt random orientations due to the parallel flow stream lines. Rotational and capillary instruments measure a fluid's response to shear deformation.

During atomization in a dual-fluid atomizer, the CWF is subjected both to shear deformation and extensional deformation. The shear rate, depending on the atomizer, is on the order of 10^4 to 10^5 sec^{-1} .⁶ Also, the particle size distribution has a substantial effect on the CWF rheology. The viscosity measurements at low shear rates (100 to 200 sec^{-1}) are not particularly meaningful. Even measurements made at moderate shear rates (1,000 sec^{-1}) do not provide useful information. For CWFs used for combustors in residential applications viscosity measurements at high shear rates experienced during atomization (150,000 1/s) have shown different values depending on coal type and beneficiation process.

The degree of dilatancy is a function of the particle size distribution and, to a lesser extent, the solids loading.⁶ The atomization process is controlled not by shearing deformations, primarily, but by extensional deformations. The shear viscosity measurements alone are therefore insufficient to predict atomization results. Elongation rather than shear breakup mechanism dominates the droplet formation process. For non-Newtonian fluids such as CWF, one cannot predict extensional viscosities based on shear viscosity measurements. Results reported in the literature suggest that the particle size distribution, stabilizers, and dispersants used in the CWF could have significant impact on the extensional rheology, which would not be readily discernible using shear rheological methods. In particular, stabilizer structure and aspect ratios of the particles present in the CWF may exert profound influences on the atomization of CWF which are undetectable by shear rheological methods. Dispersant type also appears to affect CWF extensional rheology; CWF prepared with the anionic dispersant has higher extensional resistance than the slurry formulated with a nonionic dispersant. In atomization tests carried out at MIT, it was reported that the nonionic slurry

produced a finer spray than the anionic slurry, even though the anionic slurry had a lower viscosity than the nonionic slurry. Although limited data are available on extensional rheology of CWF, this measurement may offer significant insight into correlating micronized CWF combustion data with rheological parameters.

2.1.3 Stability

2.1.3.1 Settling

The settling stability of coal water slurries has been studied by numerous investigators.^{1,2,3,7,8,9,10} These investigators have looked at correlating yield stress values to settling and stability. Two of the techniques for measuring the stability are column and rod settling methods. The critical yield stress is calculated from viscosity measurements.

Several studies^{1,2,3} have looked at ways to correlate the stability of a slurry to the measurements of the yield stress or the slurry's electrical properties, the pH and zeta potential.

Over the past several years, AMAX R&D has performed development work in this area^{7,8,9} and has determined the following factors to be important to slurry stability and rheology:

- Loading
- Particle Size
- Dispersant Level
- Chemical Stabilizer Level

From this work, AMAX R&D has developed a set of predictor equations to control these factors during slurry production.

The equation that predicts the stability of a slurry was developed from a semi-quantitative measure of the response variable "stability" defined at AMAX R&D. In this system, slurry stability is rated according to the type of sediment that forms after a given amount of time; in the development of the equation, this period of time was one month. The "stability" rating went as follows:

SP (soft-pack): A laboratory spatula sinks to the bottom of the container under its own weight; no sediment.

MP (medium-pack): The spatula sinks to the bottom of the container with only a minor assist; gelatinous cake.

HP (hard-pack): The spatula may be pushed to the bottom with a strong effort; hard cake, but resuspendable.

VHP (very-hard-pack): The spatula will not pass through the cake; not resuspendable with simple agitation.

The responses were numerically coded as 0 = VHP, 1 = HP, 2 = MP, and 3 = SP. Various tests for significance were performed on the slurry parameter variables and correlated to the response to give:

$$\begin{aligned} \text{Stability} = & - C_0 + C_1(\text{Loading}) + C_2(\text{MMD}) - C_3(\text{Loading})(\text{MMD}) \\ & + C_4(\text{STD}) + C_5(\%A-23)^2 - C_6(\%A-23) \end{aligned}$$

where "loading" is the percentage of coal plus dispersant, "MMD" is the mass mean diameter in microns, "STD" is the calculated standard deviation of the particle size distribution in microns, and "%A-23" is the percent dispersant on a coal basis. An explanation of the definitions of MMD and STD is given below. The correlation (R^2) for this equation is 0.87.

Mass mean diameter (MMD) may be thought of as the mean particle diameter calculated on a weight basis. In practice, the size distribution is approximated by determining the distribution over intervals. These intervals are determined by passing a representative sample of the distribution (pulverized coal) through a set of screens with decreasing mesh sizes (i.e., smaller openings). The weight retained on each screen gives a weight percent retained between that screen and the one above it. The MMD for the material retained would be assumed to have a mean size equal to the median of two screens.

Example 1

If a sieve test were to yield the following data:

<u>Screen Mesh Size</u> <u>Microns</u>	<u>Weight %</u> <u>Passing</u>
35	100
25	63
15	30
5	7

the mass mean diameter of the material retained on the 25-micron screen would be assumed to be $(35 + 25)/2 = 30$ microns. The mass mean diameter for this distribution would be:

$$\begin{aligned} \text{MMD} &= (35 + 25)/2 \times (1.00 - 0.63) + (25 + 15)/2 \times (0.63 - 0.30) \\ &\quad + (15 + 5)/2 \times (0.30 - 0.07) + (5 + 0)/2 \times (0.07 - 0.00) \\ &= 20.175 \text{ microns} \end{aligned}$$

The particle size distribution standard deviation may be thought of as a numerical measure of the width of the particle size distribution (PSD). The calculation is made assuming the PSD comes from the standard normal cumulative distribution. Although the actual distribution does not come from the normal distribution, the calculation for standard deviation is a measure of variability about the mean and is unbiased as an estimator of the range of particle sizes.

The calculation of the PSD standard deviation begins with the familiar form of variance calculated as:

$$s^2 = \text{Sum } (X_i - \bar{X})^2 / (n-1)$$

where Sum represents the summation over all values of X ; X_i represents an individual value of X ; and $\bar{X}$ represents the mean value of X . If X is the size of an individual particle, then the mean of X would represent the mean diameter.

Using individual particle data is not practical for this calculation. Instead, the groups of particles gathered between successive screens are used to approximate the population. In this way, the weight percent of each group can be used as a basis for the size of the group relative to the entire population. This is how the number n , the size of the sample, is dealt with. For example, if one were to extract 1,000 particles from the distribution used in Example 1, approximately 370 of the particles would fall between 25 and 35 microns, 330 particles would fall between 25 and 15 microns, etc. Since the exact diameter of each particle in a given group is not known, the entire group is assigned the value of the mean. Therefore, the calculation of variance is:

$$\begin{aligned} s^2 &= [(30 - 20.175)^2 \times 370 + (20 - 20.175)^2 \times 330 + (10 - 20.175)^2 \\ &\quad \times 230 + (2.5 - 20.175)^2 \times 70] / (1000 - 1) \end{aligned}$$

The sample, however, contains many more than 1,000 particles and (n-1) is approximately equal to n. Furthermore, if the calculation is approached term by term:

$$s^2 = (30 - 20.175)^2 \times 0.37 + (20 - 20.175)^2 \times 0.33 + (10 - 20.175)^2 \\ \times 0.23 + (2.5 - 20.175)^2 \times 0.07 = 81.4 \text{ STD} = (s^2)^{1/2} = 9.0$$

2.1.3.2 Stabilizing Agents

The CWF formulation affects the slurry stability.⁹ The selection of additives depends greatly on the extent of storage required and the end-use of the CWF from the storage tank. A major consideration in the long-term storage of the CWF is the change in the settling and viscosity characteristics with time. For extended storage, the CWF should exhibit minimum settling for several weeks. The settled material should be a soft pack and readily dispersible. The stabilizer additives used for this purpose should provide high-solution viscosities and measurable yield point at low concentrations. Also, the solid content in the CWF should be as high as possible to improve the stability characteristics. Stabilizing agents such as xanthan biopolymers can improve the stability of the CWF. Adding stabilizing agents decreases the power index and increases the yield value and the apparent viscosity. This is basically due to formation of a network structure.

Xanthan gum has been successfully used as a suspension aid in coal-water slurries to prevent coal particle settling during transport and storage. This stabilizer meets a number of performance criteria:

- (1) Prevents the settling of coal particles and the formation of a hard-packed sedimentation.
- (2) Economical to use.
- (3) Provides pseudoplastic or, at least, Newtonian rheology in aqueous solutions.
- (4) Resists degradation when exposed to high shear rates during pumping and flow through transfer lines and pipes.
- (5) Recovers its original viscosity after exposure to high shear.

- (6) Easily dissolvable in the aqueous phase.
- (7) Environmentally acceptable.
- (8) Low ash content.
- (9) Compatible with other additives.
- (10) Exceptional tolerance to pH changes during extended storage.
- (11) Not affected by high salinities.

Experimental measurements have demonstrated^{11,12} that at low shear rates slurry viscosity is dramatically increased by the addition of xanthan, thus resulting in better stability during transport or storage. At high shear rates, however, the slurry viscosity is only slightly affected due to the pseudoplastic rheology of xanthan solutions. Therefore, xanthan does not adversely affect the pumpability or atomization of these slurries even when added at relatively high use levels.

Xanthan is a polysaccharide gum derived by microbial fermentation. As such, this biopolymer is susceptible to biodegradation by the aerobic and anaerobic microbes commonly found in coal and commercial slurries. Loss of the xanthan biopolymer due to microbial attack can result in an associated loss of slurry viscosity and stability. Pfizer recommends the use of FLOGUARD 1015, an aqueous solution of formaldehyde with methanol, as a microbicide for xanthan solutions. Addition of 1.125 lb of FLOGUARD 1015 per 55 gallon barrel of slurry (1000 ppm formaldehyde) was effective in killing microbial contamination. The viscosity loss after 8 weeks was negligible and very limited settling occurred, mainly in the form of soft pack. Because it is not always possible to use formaldehyde, Pfizer attempted to identify other effective biocides. Glutaraldehyde provided initial biocidal activity in the slurry, but it must be used at high, uneconomical levels and it lacks the persistence that is necessary for protection during storage. It is, however, the only viable alternative available today.

In order to resuspend any coal particles that may settle during extended storage of CWF, the storage tank should be provided with a top-mounted agitator. The agitator must be designed to provide low-shear mixing, avoiding any local settling of coal particles. In addition, because the storage tanks are generally large it may be necessary to use several agitators of various sizes to provide proper agitation. A model test can determine agitator placement to avoid local settling.

For locations subject to freezing, the extended storage tanks should be equipped with low-density heating pads and insulation to prevent localized freezing, which might be detrimental to CWF stability. Depending on the location, the heat generated from agitation coupled with insulation may be sufficient to provide protection from freezing weather.

2.2 FUEL MANUFACTURING

Coal-slurry fuel manufacturing begins by establishing specifications the product must meet and selection of a suitable source coal that can be processed to meet these specifications. The product specifications and source coal selection are discussed in this section, which then concludes with a general description of the fuel manufacturing process.

2.2.1 CWF Specifications

The required properties of a coal-slurry fuel are specified according to the needs of the user. The fuel properties commonly specified as being of primary importance include the following:

- Viscosity at one or more shear rates.
- Maximum ash content.
- Maximum sulfur content.
- Nominal top size of the particulates.

The user may also specify the following properties, although some of these are closely related to, and cannot be changed independently of, the primary properties listed above:

- Minimum coal loading.
- Minimum heating value.
- Rheology (dilatancy/pseudoplasticity and/or power law indices).
- Stability.
- Mass mean diameter (MMD) of particulates.
- Ash composition and fusion temperatures.
- Maximum nitrogen, alkali, and trace element contents.
- Oil-compatibility and corrosion inhibitor additions.

In almost all cases, users would like to have a fuel with the highest coal loading possible while still meeting the viscosity limitations of their combustion equipment. Often, though, higher loadings entail the use of more expensive source coals, higher processing costs, and extra reagent additions, so frequently user-specific trade-offs

are made between fuel specifications and fuel cost. Similar trade-offs can occur with respect to other properties of the fuel such as the nominal top size.

2.2.2 Feedstock Selection

From the user's point of view, the most important consideration for feedstock selection probably will be the effect that the selection has on the delivered price and on the ash and sulfur contents of the fuel. The grindability, inherent (equilibrium) moisture content, and washability (mineral-matter liberation and distribution versus particle size) will be important considerations for the fuel manufacturer since each has an important impact on the yield, production cost, and product quality.¹³

In general, slurry properties are better and production costs less for fuels prepared from higher rank coals. It has been found that the low-sulfur, highly volatile bituminous coals from the Central Appalachian area of eastern Kentucky, southern West Virginia, western Virginia, and northeastern Tennessee are particularly useful for preparing high-quality micronized slurry fuels. Such fuels can have higher heating values exceeding 8,000 Btu per pound. Subbituminous and lignite coals, on the other hand, may require special thermal processing if higher heating values of more than about 5,000 Btu per pound are required.¹⁴

2.2.3 Manufacturing Coal-Water Fuel (CWF)

The basic technology for preparation of coal-slurry fuels has been well-described in the patent disclosures of Funk¹⁵ of Alfred University and in a later review of Miller.¹⁶ Manufacturers have followed a number of process flowsheets, utilizing variations of this technology for fuel preparation. The better known producers of boiler-grind fuel in North America have been Carbogel,¹⁷ Slurrytech/Ashland/Babcock & Wilcox (Co-AL),¹⁸ Atlantic Research (ARC-COAL),¹⁹ Advanced Fuel Technology/Sohio, CoaLiquid, Fluidcarbon, and OXCE.^{20,21} United Coal Company, Otisca, and AMAX R&D specialized in micronized grades. The system followed by AMAX R&D is representative of the basic flowsheet used by most of these manufacturers and is described next.

At AMAX R&D Center in Golden, the coal-slurry fuel is usually manufactured from the prepared coal normally shipped from a source mine or preparation plant. Most such coal has been crushed to passing 2 inches before sale. It is crushed further at Golden to passing 5/8 inch. The crushed coal is washed in a heavy-media separation circuit at a low specific gravity if a deep-cleaned, low-ash grade of fuel is required. The crushed, or crushed and deep-cleaned, coal is next ground with water and dispersant sequentially in a tumbling

ball mill to passing 0.5 mm and in a stirred ball mill to passing the specification particle size. Operating conditions during the two grinding steps are adjusted as needed to provide the desired particle size distribution for acceptable product rheology and stability. At times, the target particle size distribution is accomplished by grinding a portion of the slurry separately to a finer size and recombining the two portions afterward. The principal operating controls during the grinding stages are the feed rate to each, the slurry viscosity in the mills, and the diameter of the grinding media in the stirred ball mill. Since additional pulp dilution is undesirable, the primary method of controlling viscosity is by adjusting the amount of dispersant added during each grinding step.

A final adjustment of the slurry loading and reagent additions is made as a last step to insure that the fuel meets customer rheology and stability specifications. An ammonium naphthalene sulfonate (A-23) is most commonly used as an anionic dispersant, and a xanthan gum (Flocon) is used as a stabilizer. Other reagents are added at times to meet specific customer requests. The latter additives include biocides, corrosion inhibitors, and reagents to insure oil-compatibility and for pH adjustment. Fluxes may also be included in the formulation to modify the slagging properties of coal ash.

Slurry fuel producers who use froth flotation for deep cleaning include a dewatering step (commonly employing either a filter or a centrifuge) in the flowsheet.¹⁷ Depending upon the type of grinding equipment employed, some producers may also blend slurries ground to differing degrees in order to optimize the particle size distribution of the finished product and produce "bimodal" or "packed" slurries.¹⁶ Special equipment is often required to accomplish this blending because of the high viscosity of the component slurries and/or filter cakes.

The AMAX chemical cleaning system²² includes leaching and pressure filtration steps between the initial tumbling ball mill grinding and the finished stirred ball mill grinding. Chemical cleaning removes more of the ash than possible by physical cleaning alone.

A very large number of dispersants have been used or proposed for use during preparation of coal-slurry fuel.^{16,23,24} Most of these are organic compounds which can be placed into one of two classes, anionic and nonionic. Both classes are believed to function by absorbing onto surfaces, preventing interparticle contact. The anionic dispersants such as ammonium naphthalene sulfonate tend to form negative ionic charges on the surfaces so that the particles repel each other. The nonionic dispersants, on the other hand, tend to coat the surfaces with long-chain molecules which hold the particles apart. Usually anionic dispersants are less expensive and are effective at lower dosages than nonionic dispersants.

The rheology of fuels prepared with nonionic dispersants may also be more sensitive to changing temperature than fuels prepared with anionic dispersants.

Fewer stabilizer reagents have been proposed.¹⁶ The xanthan gums such as Pfizer Flocon are by far the most popular. A 0.5 percent attapulgite clay addition has been shown to be equally effective.²⁵ The differences in stability between fuels prepared from differing source coals and from coals cleaned by different methods often may be due to the differences in the amount of residual clay in the fuels.

2.3 HANDLING AND TRANSPORTATION STUDIES OF CWFs BY PERFORMING ORGANIZATIONS

There were several important reports issued during the mid-1980s concerning the transportation and handling properties of coal-slurry fuel. Pumping characteristics and materials of construction were touched upon in this reports. One of the reports, from the TRW Space and Technology Group, concerned DOE-sponsored testing to generate a database for the design of fuel delivery systems for furnaces and boilers, and the other, from Atlantic Research Corporation, described their experience in handling the fuel. These reports and others are reviewed below. AMAX R&D's experience in handling CWF is described in the final part of this section.

2.3.1 TRW Space and Technology Group

TRW^{26,27} compared the behavior of six different lots of slurry fuel (from three manufacturers). Their work included pump loop testing simulating a 30 to 300 million Btu per hour boiler operation and is particularly applicable to bulk handling systems for supplying Tecogen residential and commercial customers, since the base case slurry used by TRW for much of the testing - nominally minus 200 mesh (75 micrometers) - was unusually fine for a boiler fuel. TRW arrived at the following conclusions:

1. Slurry fuels can be stored for long periods with remarkable stability. TRW did observe differences in stability between fuels from different sources and also an improvement in the properties of successive lots of fuel from the same producer during the 1982 to 1986 time-frame of the investigation. They found that slurry fuels can be pumped around with little change in solids content, particle size distribution, pH, or viscosity.
2. The Metzner-Reed model for homogeneous, non-Newtonian fluids is applicable to slurry fuels. Pressure losses in piping systems can be estimated by using the conventional Fanning friction factor-Reynolds

number relationship, with the Metzner-Reed Reynolds number in place of the Newtonian Reynolds number. The Metzner-Reed Reynolds number, Re_{MR} , is defined as follows:

$$Re_{MR} = \frac{DpV}{\mu_e} = \frac{D^{n'}V^{2-n'}p}{K'g^{n'-1}}$$

where D is the pipe diameter, p is the slurry density, V is the fluid velocity, μ_e is the effective slurry viscosity, and n' and K' are the flow behavior index and the flow consistency index, respectively, in the power law representation of the shear stress/shear rate rheogram of the slurry.

3. Progressive cavity and twin screw pumps are well suited for coal-water slurry fuel high-pressure applications. TRW based this conclusion upon observation of 1,520 hours of service for the progressive cavity pump and 1,270 hours service for the twin screw pump, both discharging against 400 psig. Based upon the results of post-test teardowns of the pumps, TRW recommended improvements to the mechanical seals and additional flush water to stuffing boxes.
4. A lobe-type pump and a compressed air operated diaphragm pump performed satisfactorily for slurry transfer service. Considerable wear was seen on the tungsten carbide coated internals of the lobe-type pump after 2,500 hours of service, and it was recommended that mechanical seals with water flushing be installed rather than packing glands in such pumps. No problems were encountered with the diaphragm pump except for an inadequate supply of compressed air at the test site. Diaphragm pumps do not have rotating shafts or moving pistons requiring seals.
5. Carbon steel is an acceptable material of construction for coal-slurry fuel applications. Erosion/corrosion rates of approximately 10 mils per year were seen on carbon steel wear plugs during the 2,300-hour pump loop testing. Stainless steel and either hardened or hard-coated steel were recommended for certain critical internal parts of pumps and valves. Other materials (fiberglass, ceramic linings, and elastomer linings) also provided good service.

6. Commercial instrumentation is available and suitable for slurry fuel systems. In many cases, it is important to provide proper isolation of pressure transducers and similar components from the slurry.
7. Sufficient test data and operating experience are available for the design of coal-slurry fuel delivery systems for commercial boiler installations.

2.3.2 Atlantic Research Corporation

In general, Atlantic Research Corporation's experience²⁸ in handling CWF boiler fuel on a large-scale semicommercial basis matched the experimental observations of TRW. During the course of their fuel marketing effort, Atlantic Research made a 4,000-gallon shipment by tank truck to California, a 900,600-gallon shipment by railroad tank cars to Pittsburgh, and a 94,000-gallon shipment to Boston by barge. The coal-slurry fuel activities of Atlantic Research have since been turned over to Arctech Corp. The published paper²⁸ made the following specific points:

1. Formulation and Stability of Fuels

Coal-water fuels can be formulated for reasonable storage periods. Agitation is recommended for storage of longer than 90 days. Phase separation can be corrected with stabilizing additives which promote formation of a yield point.

2. Slurry Viscosity

The viscosity of a given slurry will vary with temperature, shear history, particle size, shear rate, and solids loading. Dilution is a particularly attractive method for lowering the viscosity at the point of use and is less expensive than adding more dispersant reagent to the mixture.

3. Handling Pointers

Care must be taken in the handling of the fuel to avoid changes in the chemistry and viscosity. Particle size degradation, evaporation of water, overheating, and oil contamination can be significant problems and should be avoided. Atlantic Research saw CWF deposits on steam coils due to local boiling and recommended hot oil or glycol-water systems as being less likely to cause overheating than steam heating systems would for controlling viscosity and prevention of freezing. (AMAX R&D uses a patented additive package in fuels it provides for applications where oil contamination is likely to occur.)

4. Storage

Agitators in storage tanks should be geared for low tip-speeds and designed to provide vertical movement of the slurry. A representative design criterion is 0.02 kW per ton coal. Vertical baffles spaced away from the walls are desirable. Recirculation alone is not very efficient and can result in wide fluctuations in the fuel viscosity. Storage tanks should have closed tops with pressure/vacuum relief valving. Tanks and agitators can be carbon steel, but fiberglass or epoxy coatings will minimize solids deposition on the walls. Tank insulation and an external indirect heat exchanger system may be required to maintain the temperature of the fuel.

5. Rail and Truck Transportation

Both rail and truck transportation have been successfully demonstrated. The tanks should be insulated and, if possible, fitted for air pressurization to assist unloading. Lining rail cars with an epoxy coating is recommended to facilitate cleanup with spray systems. The use of stainless steel tanker trucks with a minimal number of compartments is recommended for short hauls. Aluminum tankers can be used but slurry additives may slowly oxidize the metal.

6. Pumps

Progressive cavity (especially Moyno-type) pumps are used successfully in most situations since they develop low shear rates. Other types such as gear, lobe, centrifugal, and screw pumps were acceptable for limited applications and at lower solids loadings. Pumps should be operated at slow speeds, and abrasion resistant material used for all rotating parts. Brass and bronze wetted parts should be avoided. CWF compatible materials include nodular iron, carbon steel, stainless steel, Buna N, natural rubber, Neoprene, and many polymers such as fiberglass, Teflon, Viton, and polycarbonate.

7. Piping and Valving

At high solids loading service, Atlantic Research designed piping and valves for laminar flow of CWF with velocities of 3 to 5 feet per second. Velocities of 7 to 8 feet per second could have been used at intermediate CWF loadings. They recommended that valve pressure drops be kept low to avoid erosion. At the time the paper was written, their designs

utilized variable speed pumps rather than control valves for flow control, since all of the control valves which they tested failed when pressure drops exceeded 40 psi. Atlantic Research used Newtonian assumptions with standard design equations. To avoid settling problems, they recommended that all piping be pitched, dead-legs be avoided, and sufficient drains and rod-out ports be provided.

2.3.3 Electric Power Development Company (Japan)

Pipeline testing of boiler grade CWF was reported by a group²⁹ in Japan. Piston, screw, and centrifugal pumps were compared in 2-, 4-, and 10-inch diameter test loops up to 260 feet long. Their conclusions follow:

1. Pump Pressures

Pressure loss in a straight pipe can be estimated from rotational viscometer data using a relationship somewhat resembling the Metzner-Reed equation described by TRW:

$$\text{Modified Reynolds Number} = Re_m = \frac{8 (D^{n'} V^{2-n'} p)}{K'} \left[\frac{n'}{6n' + 2} \right]^{n'}$$

$$\text{Friction Factor} = f = 16/Re_m$$

where D, V, p, n', and K' are the same variables as defined above by TRW for the Metzner-Reed equation.

They found that slurry left in the test loop for 7 days could still be pumped.

2. Types of Pumps

Piston, screw, and centrifugal pumps were all usable for CWF. The centrifugal pumps tended to be less efficient than the other two, and the screw pump seemed to increase the viscosity of the slurry more than the piston pump. The increase in viscosity could be overcome by adding more dispersant to the fuel.

3. Stabilization

A second paper³⁰ by the Japanese group reported that carboxymethylcellulose, xanthan gum, and attapulgite (a clay mineral) were effective stabilizing agents for CWF. Predictable relationships between stabilizer additions and slurry pumping properties were observed.

2.3.4 Bechtel Power Corporation

Bechtel³¹ presented guidelines for designing CWF handling systems. Most were consistent with the TRW and Atlantic Research papers. Air and/or water flushing and pigging systems were given considerable attention. In-line strainers were suggested to remove tramp material. Recirculation was not considered to be effective for large tanks, and either axial or radial flow agitators were recommended when mixing would be needed.

Seven large scale CWF demonstration firings were reviewed in a subsequent Bechtel paper.³² No serious problems were reported relating to either the transportation or handling of any of the fuels. (In one instance, a separate EPRI summary³³ did say that cleaning the railroad tank cars was a more difficult task than expected.)

Bechtel personnel also coauthored a report³⁴ with Atlantic Research and Boston Edison personnel which described the barge shipment of CWF from Virginia to Boston for a test burn at the Mystic No. 4 Station. The fuel contained 70 percent minus 0.6-mm coal and had a viscosity of 1,000 cP. The CWF was unloaded with two 60-gpm air operated diaphragm pumps operated by a portable construction type air compressor. Each pump had a 25-foot, 3-inch rubber suction hose for drawing the fuel from the barge tank to the pump. Standard 3-inch cloth fire hoses, 200 feet long, connected the pumps to the three 22,500 truck-mounted storage tanks. There were no slurry plugging problems noted during the unloading operation, although some problems were reported with ice crystal formation in the compressed air lines.

A 25-gpm Moyno pump was used to supply the burners. All piping was schedule 40 carbon steel with socket welded or threaded joints. The piping was sized for slurry velocities of less than 2 feet per second and air and water flushing connections were provided at various points. The lines were blown out with air and pre-wetted with water before filling with CWF. The pipeline to the burner included two isolatable pressure-relief valves, a strainer, and a return line to the fuel tank.

Rupture discs would have been preferred over the relief valves had they been available in time.

2.3.5 EPRI/Du Pont/Babcock & Wilcox

EPRI sponsored a 35-day test burn in a 60,000-pound/hour steam boiler operated by du Pont in Memphis.^{35,36} The trial was considered to be very successful. The fuel (from two sources) was delivered in 24 railroad tank cars with no problems other than the tank car cleaning problem alluded to above. The slurry was transferred from the rail cars to the 15,000-gallon day tank near the boiler by trailer truck. The trucks were loaded by a diaphragm pump connected to the rail car with a hose. The inlet to the pump contained a strainer with 3/16-inch holes. The strainer accumulated a small amount of soft sludge and was cleaned after each car was emptied. One of the fuel vendors³⁶ claimed that less than 1/10 of 1 percent of the material had settled after 23 days and 1,053 miles of rail travel. The same vendor also claimed that the emptied cars were easily cleaned by using an air and water spray system called a "tiger."

The day tank near the boiler was equipped with a 45-rpm 10-hp agitator with blades at two levels in the 18-foot high tank. The tank had 4 vertical baffles as well. The agitator operated continuously. The slurry was withdrawn with a Moyno pump which recirculated to the tank when the boiler was not in operation or when operating at low firing rates. There was a dual basket strainer in the discharge line which was cleaned each shift and frequently found to contain hardened sludge with some apparently fibrous matter.

The piping system was designed to minimize the chances of the slurry settling out. No air was allowed to contact the slurry and the entire system was flushed with water and air whenever the piping system was to be opened. Connections were also bled during a startup to purge residual air and water from the system. Periodic purging of unused connections was also recommended.

Overpressure protection for the piping system was a problem. Standard relief valves were not reliable due to accumulations in the spring area. A diaphragm-type safety valve might have been successful, but there would have been a chance of pluggage in the stagnant vent line. High pressure switches and interlocks were provided in the system instead.

A Rosemont magnetic flow meter and a Micro-Motion mass flow meter performed equally well. The Micro-Motion flow meter indication was usually within 1 percent of the flow calculated from the combustion results.

The slurry fuel eroded internal atomizer parts made of standard materials rather rapidly. Tungsten carbide surfaces were satisfactory, but all contact surfaces must be coated. There was no measurable wear found on the Moyno pump after the 1,500 hours or so of operation.

2.3.6 Valleydale Packers

Experiences from a CWF boiler-firing demonstration in Virginia were described.³⁷ The CWF firing occurred over about a one-month period. The fuel was received and stored on-site in a four-compartment tanker trailer, and 7,000 gallons were burned at a rate of about 3 gallons per minute. Periodic recirculation and occasionally portable agitators were used to keep the coal in suspension. A Moyno progressive cavity pump was used. CWF viscosity increased considerably when the temperature freeze/thaw approached the freezing mark, and the fuel line actually froze solid when the temperature dropped to 20°F for several hours. The rheology returned to normal when the CWF thawed. The average temperature of the CWF during the firing was 41°F and there was no preheating before combustion.

2.3.7 Adelphi University

Pump loop testing was done on five boiler-grade slurry fuels.³⁸⁻⁴⁰ Centrifugal pumps were satisfactory for once-through transfer service but not for recycle/recirculation service where positive displacement pumps caused less degradation of slurry properties. The investigators found that continuous agitation thickened fuels from some, but not all, manufacturers. Adelphi also tested the use of pigs for cleaning pipelines. Both low- and high-density polyurethane pigs performed very well and greatly reduced the amount of flushing water required when changing fuels.

Adelphi also looked at the effect of storage temperatures and freeze/thaw cycling on laboratory quantities of CWF for several sources.⁴¹ In most cases, there was little permanent change in the rheology or stability. The observations of another group⁴² on one slurry were similar to the Adelphi results.

2.3.8 DOE/University of Pittsburgh

Pump loop tests were made with water and water-methanol slurries prepared from boiler-grind coal.⁴³ An excellent correlation was shown between a friction factor, f_m , and the Metzner-Reed Reynolds number, Re_{MR} , described earlier:

$$f_m = 16/Re_{MR}$$

2.3.9 Universite de Technologie de Compiègne/Elf Aquitaine

A correction term was developed to allow for the additional flow through a long pipe due to the wall slippage phenomena.⁴⁴ The group also studied the effect of temperature on the rheological and stability properties of a coal-slurry fuel.⁴⁵

2.3.10 Combustion Engineering/OXCE Fuels

C-E⁴⁶ described receiving test burn quantities of slurry fuel from Sweden which had been shipped in pressurizable containers. The containers were shipped by truck from the port to the test facility in Connecticut. Pressurized rail cars were also used for shipping slurry to a Canadian demonstration. C-E installed tungsten carbide inserts to make their atomizing system "erosion-resistant." They stressed the importance of pre-wetting fuel lines before use and flushing them afterward. Close monitoring of pumps and fuel control valves for wear was also found to be important.

OXCE Fuels⁴⁷ reported the results of pumping tests in the laminar flow region. Apparent viscosities calculated from the Hagen-Poiseuille formula correlated pressure drops and flow rates through various lengths of 2- and 1-inch pipes. Similar tests in a 1/2-inch pipe were planned. The equation for calculating apparent viscosity, μ_A , from the Hagen-Poiseuille formula was given as follows:

$$\mu_A = (\Delta P d / 4 L) / 8 V d$$

where ΔP is the pressure drop, d is the pipe diameter, L is the pipe length, and V is the mean velocity of the slurry in the pipe.

2.3.11 AMAX R&D Experience

Since 1983, AMAX R&D has prepared various quantities and grades of CWF for a variety of customers. Most of the production has consisted of multi-drum lots of micronized slurry prepared from eastern high volatile bituminous coals, but other coals have been processed as well, including subbituminous and lignites.

The stability of the slurry has always been an important concern for users of coal-slurry fuels. Some settling has always been accepted, in fact expected, and users of AMAX R&D fuel routinely plan to remix the fuel shortly before use just as they would latex paint. An important consideration for AMAX R&D has been to avoid distribution of slurries that might settle to a hard-packed cake that a user

would have trouble redispersing. Preparation of an acceptable fuel for customer use has been found to be largely a matter of achieving a balance between the particle size distribution and coal loading and the dispersant and stabilizing reagent additions. Achieving this balance has proven to be something of an art because the balance does vary from one coal to another.

Most of the problems which users have reported can be traced to either of two handling problems: 1) prolonged recirculation or agitation, which seems to destroy the effectiveness of the dispersant and stabilizer; and 2) prolonged exposure to the atmosphere, which allows evaporation of the liquid phase. The latter condition results in the formation of skins and clots of hardened slurry which do not disintegrate easily during mixing. Skin formation is especially likely with newly prepared, highly loaded slurries. There is a significant temperature rise during grinding which raises the vapor pressure of the liquid phase, and the loss of even a small amount of the liquid by evaporation will change the surface of the slurry from a fluid to a solid cake. The problem does not seem to arise when fuels are diluted slightly, kept well mixed while cooling, and stored in closed drums or tanks.

Allowing the formation of a vortex during intense mixing has been found to result in considerable air entrainment in some fuels. Significant volume expansion occurs, and the slurry takes on the consistency of whipped cream. (Air entrainment is also a problem when preparing CWF from dry pulverized coal according to the OXCE Fuel Company.²¹⁾

Most slurry transfers in the AMAX R&D pilot plant are done with air-operated diaphragm pumps. These pumps are convenient to use and have provided efficient, reliable service. Similar pumps are widely used at construction sites and for pumping a variety of industrial thickener and clarifier sludges. Moyno progressive cavity pumps are used in the pilot-plant circuits for high-pressure service such as feeding slurry to the stirred ball mill.

No unusual corrosion or erosion problems have been encountered during CWF production at AMAX R&D. The fuel is normally shipped in epoxy-lined drums to avoid contamination. Open-head drums are supplied which allow the user to insert a portable mixer directly into the container. AMAX developed a Material Safety Data Sheet (MSDS) for CWF in 1985.

3. FUEL PREPARATION

CWF specifications involve several trade-offs, as discussed in Section 2.2.1. In general, the highest possible coal loading that has reasonable viscosity for handling and atomization and good stability would be desirable. The other factor is minimization of preparation costs which include the degree to which the coal must be ground and the additives (dispersant and stabilizer) required.

Three parent coals and five different beneficiation techniques were selected. A nominal fuel specification was established. Seven different coal water fuels were prepared using combinations of coals and cleaning techniques.

3.1 NOMINAL FUEL SPECIFICATIONS

The parent coals used were Upper Elkhorn No. 3, Illinois No. 6, and Wyodak. The Upper Elkhorn No. 3 was chosen as the base coal since Tecogen has extensive working experience with it. The Illinois No. 6 coal was chosen due to the large reserves of the coal and its high sulfur content. The Wyodak coal was chosen as a representative western subbituminous coal. The sources of these coals are listed in Table 3.1. Analyses of representative samples of the as-received parent coals are given in Table 3.2.

Seven slurries were made from the three parent coals using different beneficiation techniques. A nominal fuel specification giving the desired coal/water slurry characteristics is shown in Table 3.3. The following five (5) cleaning processes were used.

- Heavy media separation
- Heavy media separation with water leaching
- Chemical cleaning
- Oil agglomeration
- Froth flotation

Table 3.4 lists the cleaning processes used for each parent coal.

3.2 BENEFICIATION PROCESSES

The following sections give a description and process flow chart of each beneficiation technique used to clean the parent coal.

TABLE 3.1
SOURCE COALS

	Rank	Source
Upper Elkhorn No. 3	hVA	Wentz Plant, Virginia Westmoreland Coal Company
Illinois No. 6 (HMS)	hVC	Delta Mine Marion, Illinois AMAX Coal Company
Illinois No. 6 (Agglo)	hVC	PETC Sponsored Testing by Bechtel at CQ, Inc., Homer City, Pennsylvania
Upper Wyodak (Roland Seam, Power River Basin)	sub C	Eagle Butte Mine Gillette, Wyoming AMAX Coal Company

TABLE 3.2
REPRESENTATIVE ANALYSIS OF AS-RECEIVED PARENT COALS
(Dry Basis Except for Moisture)

	Upper Elkhorn No. 3	Illinois No. 6	Upper Wyodak
Moisture	8.0	11.0	3.0
Ash	2.72	10.8	7.7
Volatile Matter	36.32	35.9	42.2
Fixed Carbon	60.96	53.4	50.1
Sulfur	0.7	2.9	0.7

TABLE 3.3
NOMINAL FUEL SPECIFICATIONS

Loading	Greater than 55%
Heating Value	8000 Btu/lb slurry
Viscosity	200 cp at 100 1/s
Rheology	Pseudoplastic to Newtonian at shear rates to 1000 1/s
Ash	Less than 1%
Sulfur	Less than 0.7%
Top Size	98% minus 325 mesh
Mass Mean Size	9 to 11 micrometers
Stability	No significant settling in 30 days

TABLE 3.4
CLEANING PROCESS AND SOURCE COAL MATRIX

Cleaning Process	Source Coal		
	Upper Elkhorn	Illinois	Wyodak
Heavy Media Separation	X	X	X
Heavy Media Separation with Water Leaching	X		
Chemical Cleaning	X		
Oil Agglomeration		X	
Froth Flotation	X		

3.2.1 Heavy Media Separation

The heavy media separation technique (HMS) is depicted in the flow chart given in Figure 3.1. Coal is received and crushed to pass through a 5/8-inch screen prior to being fed to the heavy media separation stage. In the HMS stage, water and a magnetite slurry are added. The HMS unit is a stirred conical vessel with the feed entering tangentially in a cyclonic manner. Two streams leave the HMS unit – the product and the waste. The waste material is discarded along with the fines (minus 14 mesh) material. The product (cleaned coal) is fed to the initial grinding stage, then water and dispersant are added to facilitate the grinding. The product is ground to minus 0.3 mm. The ground product is micronized in a Draiswerke stirred ball mill. Additional dispersant may be added in the Draiswerke mill to lower the viscosity and facilitate micronization. The micronized product is mixed into a slurry of the desired formulation by the addition of stabilizers, water, and dispersant. The resulting slurry is tested for stability and viscosity, then shipped.

3.2.2 Chemical Cleaning

The chemical cleaning circuit process units are shown in Figure 3.2. The circuit is also used to make the HMS water leached product as well. The first four process steps produce a ground HMS product as previously discussed. The ground HMS product is pressure filtered and fed to an autoclave where a 10-percent sodium hydroxide solution is added. This process step operates at 450°F. Much of the ash is dissolved in this step and washed out of the product stream in a rinsed pressure filtration step. The filtered product is fed to a second autoclave operating at 175°F. A 10-percent solution of hydrochloric acid is added to dissolve the ash materials not removed by the caustic step. The product is pressure filtered and rinsed. Finally, the product stream is fed to a hot-water high-pressure wash at 450°F and filtered. The filtered product is reslurried and micronized in the Draiswerke stirred ball mill. The slurry is adjusted to the desired formulation. For the water leached product, the material will be fed straight from the initial grinding stage to the hot-water high-pressure wash stage through a pressure filtration step.

3.2.3 Froth Flotation

The flotation product will also be made and processed into a slurry. The flotation circuit process stages are shown in Figure 3.3. As for the HMS products, mine production coal will be received and crushed to minus 5/8 inch in size prior to going through the initial grinding stage in the 4-foot by 4-foot ball mill. This material then flows through the froth flotation system. The clean product is pressure filtered and resuspended. Final grinding is then done in the Draiswerke

Figure 3.1 No Cleaning or HMS Cleaning

Figure 3.2 Chemical Cleaning

Figure 3.3 Froth Flotation Cleaning

stirred ball mill to obtain the micronized product. Dispersant may be added to the Draiswerke mill to lower the viscosity and facilitate micronization. The micronized product is adjusted to final slurry specifications by the addition of stabilizer, water, and dispersant.

3.2.4 Oil Agglomeration

The cleaning technique by oil agglomeration is based upon the difference in surface properties (water and oil wettability) between particles of clean coal and particles of refuse. The flow chart of the oil agglomeration process is presented in Figure 3.4. A bridging oil (5 to 30 percent of coal by weight) is vigorously mixed with the coal slurry. The oil wets the coal particles, displacing the water, and the oil-coated particles stick together. The balls of oil-coated coal particles grow larger as mixing continues. Agglomerated coal pellets are separated from slurry of fine refuse by screening. Several different types of oils may be used in the process including heptane, pentane, diesel fuel, No. 6 fuel oil, and asphalt products. However, a larger proportion of the oil used in the agglomeration process consists of lighter oils. Petroleum asphalt binder is added to assist in enlarging product agglomerates. In some instances the bridging oil can be recovered by thermal treatment of the agglomerated product.

3.3 CWF CHARACTERISTICS AND PROPERTIES

In preparing the seven (7) coal water slurries the specifications used are given in Table 3.3. Since some of the parameters are interrelated two prime parameters were selected; loading and top size. Ash and sulfur content were dependent on the cleaning process and parent coal. The viscosity was adjusted by the addition of A-23 dispersant.

The properties of the prepared coal water fuels are given in Tables 3.5 and 3.6. The properties for the bituminous coal approached or exceeded the nominal fuel specifications. The Upper Wyodak loading and heating value were not achieved. The CWFs made with Illinois No. 6 had a sulfur content that was higher than the specification due to its high organic sulfur content.

Table 3.7 lists the densities and some rank-related properties of the test coals. The calculated densities of ash-free water-saturated particles of the three coals were all about the same. (These calculations do not take into account any swelling that might occur when coal particles absorb water.)

The heavy media separation/filtration (HMS/filtration) sequence was included in the comparison of the beneficiation processes so that it could be

Figure 3.4 Oil Agglomeration

TABLE 3.5
PROPERTIES OF COAL WATER FUELS

	UE-HMS	UE-M&F	UE-CC	I-HMS	I-OA	W-HMS	UE-FL
Fuel Analysis, %							
Coal	53.90	53.90	53.60	54.00	51.80	40.60	54.32
Water	45.87	45.81	46.18	45.55	47.03	57.78	45.43
Additives	0.23	0.29	0.22	0.45	1.17	1.62	0.25
Dry Coal Composition, %							
Ash	1.52	1.62	0.39	5.89	3.54	5.75	1.50
Volatile Matter	34.60	34.70	34.56	37.92	40.63	44.86	34.77
Sulfur, %	0.8	0.8	0.8	2.5	2.8	1	0.8
Additives, % of Dry Coal							
A-23 Dispersant	0.37	0.47	—	0.99	—	4.00	—
Flocon Stabilizer	0.05	0.08	—	None	—	None	—
Fuel Viscosity, cP							
at 100 1/s	190	200	200	200	175	410	200
at 500 1/s	240	310	355	275	240	290	240
at 1,000 1/s	240	260	345	285	245	255	240
Mass Mean Diameter, Micrometers	12.1	13.2	12.0	11.4	10.3	17.0	10
Particle Size Distribution, % Passing							
75 Micrometers	99.7	99.7	99.63	99.8	99.71	95.4	99.73
45 Micrometers	98.2	98.3	97.93	98.7	99.57	93.2	98.47
30 Micrometers	93.1	93.9	93.18	95.7	99.34	87.7	94.69
20 Micrometers	83.2	81.6	86.53	86.9	97.28	74.4	86.52
10 Micrometers	55.2	47.9	52.31	53.0	53.12	51.8	58.96
4 Micrometers	28.2	22.6	23.97	38.3	22.36	29.7	27.48
1 Micrometer	2.8	2.7	2.68	5.1	2.30	5.2	3.74

TABLE 3.6
HEATING VALUES OF COAL WATER FUELS

Source Coal	Higher Heating Value, Btu/lb		
	Slurry	Dry Basis	Moisture and Ash-Free
Illinois No. 6 HMS	7390	13572	14089
Upper Wyodak HMS	4935	11688	12401
Upper Elkhorn HMS	8190	15131	15365
Upper Elkhorn HMS/Filtered	8166	15070	15318
Upper Elkhorn CC	8201	15238	15298
Illinois No. 6 OA	7109	13421	13914
Upper Elkhorn Flotation	8243	15105	15335

TABLE 3.7
SIGNIFICANT PHYSICAL PROPERTIES OF BENEFICIATED COALS

Property	Upper Wyodak	Illinois No. 6	Upper Elkhorn
ASTM Rank	Subbituminous "C"	High Volatile Bituminous "C"	High Volatile Bituminous "A"
Volatile Matter, MAF %	47.6	40.3	35.2
Equilibrium Moisture, AF % ^a	29.73	7.32	2.14
Density Dry Coal, MAF g/cc	1.429	1.286	1.253
Estimated Pore Volume, Wet Coal, AF cc/cc	0.377	0.092	0.027
Calculated Density, Wet Coal, AF g/cc	1.267	1.260	1.246
Estimated Effective Density of Ash, g/cc	2.70	2.70	2.70

^aAt 96 to 98% relative humidity and 30°C.

MAF = Moisture and ash free.

AF = Ash free.

determined whether washing certain metal ions from the coal would improve the dispersion and stability of the product slurries. As it turned out though, very little difference was observed between the properties of the Batch C (HMS) and Batch D (HMS/filtration) fuels and also between the blended HMS and HMS/filtered slurries during storage tests with and without chemical stabilization. This similarity is probably to be expected since the particle size distributions of the Batch C and D fuels and also the ion concentrations in the aqueous phase are very similar. The metal ion concentrations in Table 3.8 were determined by ICP spectroscopy on filtrates from the respective slurries. These data were for Upper Elkhorn coal. Certain other coals are known to contain soluble materials (such as sodium chloride and ferrous sulfate) which would be removed by such a filtration procedure.

TABLE 3.8

CONCENTRATION OF COMMON ELEMENTS IN AQUEOUS PHASE
OF COAL SLURRY FUELS PREPARED FROM BENEFICIATED UPPER ELKHORN COAL

Element	Concentration, ppm	
	HMS	HMS/Filtered
Ag	<0.03	<0.03
Al	0.08	0.21
As	<0.01	<0.01
B	0.47	0.35
Ba	<0.05	<0.05
Bi	<0.01	<0.01
Ca	13	19
Cd	<0.005	<0.005
Co	0.01	0.01
Cr	<0.005	<0.005
Cu	0.09	0.04
Fe	0.02	0.01
K	17	12
Mg	2.3	2.8
Mn	0.03	0.07
Mo	0.77	0.27
Na	103	88
Ni	0.14	0.05
P	0.18	0.08
Pb	<0.05	<0.05
S	106	110
Sb	<0.01	<0.01
Se	<0.01	<0.01
Si	<0.77	<0.75
Sn	<0.02	<0.02
Sr	1.0	1.4
Ti	<0.01	<0.01
V	<0.01	<0.01
W	0.11	0.07
Zn	0.008	0.027
Zr	<0.01	<0.01

4. BULK STORAGE

Bulk storage is defined as the operation following the preparation of the CWFs and prior to transportation to user sites. There exists commonality between bulk and residential storage. Residential storage consists of storage of CWF at a smaller scale. In both cases, the main objective of storage is to maintain the CWFs in a fully suspended state or ready-to-use status. Two methods can be used to keep a CWF fully suspended: resuspension by mechanical agitation and/or chemical stabilization.

Experimental testing examined CWF resuspension and chemical stabilization. Two hundred fifty (250) gallons of each slurry were used to prepare the samples. The 250 gallons consisted of four batches of each slurry ground by differing degrees. Particle size distributions were made on each batch and the batches were blended to give mass mean diameters of 9 μm and 13 μm with comparable size distributions.

4.1 CHEMICAL STABILIZATION

Table 4.1 lists the storage test results with the CWF characteristics. Slurries of each of the beneficiated test coals were formulated with two particle size distributions and varying additions of Flocon stabilizer and were stored for two months. The condition of the sediment in each of the containers was determined periodically and a rating was given concerning its resuspension properties. The best rating, 3, was assigned to slurries in which most of the sediment occurred as a soft-pack cake which could be resuspended very easily. The poorest rating, 0, was assigned to slurries in which a very hard-pack cake formed which was extremely difficult to resuspend. Table 4.2 gives a detailed breakdown of the rating system.

Adding Flocon (a xanthan gum) to a slurry formulation changed the properties of the sediment as it formed from a hard-pack type to a soft-pack type. A few slurries without Flocon remained easy to resuspend over the entire 2-month storage period, but most did not. All of the slurries that did form a hard-pack cake without Flocon benefitted from the addition of Flocon. The minimum amount of Flocon required for maintaining an easily resuspended soft-pack sediment for at least 2 months could be estimated from the storage data and was found to depend on the coal type, beneficiation process and particle size distribution. Table 4.3 contains a summary of the chemical stabilization for 2-month storage test results.

Figures 4.1 to 4.11 are graphs of the stabilizer (Flocon) required to provide 2-month stabilization versus several different parameters. Figure 4.1 gives the

TABLE 4.1

STABILITY OF SLURRIES CONTAINING ADDED CHEMICAL STABILIZER

Source	Batch	Beneficiation	Coal By Wt	MMD	Rosin-Rammler Parameters		Reagents, ppm		Viscosity, cP			2-Month Stability Rate
					n	k	A-23	Flocon	100 s ⁻¹	500 s ⁻¹	1000 s ⁻¹	
Wyodak	B	HMS	40.6	17.0	0.798	14.71	16200	0	410	290	255	3
Wyodak		HMS	35.8	12.6	1.002	12.23	7160	0	310	130	100	3
Wyodak		HMS	34.0	9.0	0.856	7.98	10200	0	320	130	100	3
Illinois 6	A	HMS	53.1	11.4	1.097	11.35	5310	0	200	275	285	1
Illinois 6		HMS	54.4	13.0	1.074	13.01	3910	0	200	280	280	2.5
Illinois 6		HMS	54.3	13.0	1.074	13.01	4450	100	200	340	370	2.5
Illinois 6		HMS	54.2	13.0	1.074	13.01	4710	200	200	300	280	2.5
Illinois 6		HMS	54.1	13.0	1.074	13.01	5100	400	220	260	260	3
Illinois 6		HMS	53.1	8.8	0.916	8.20	7630	0	200	250	260	3
Illinois 6		Agglom	51.8	10.3	1.195	12.60	11400	0	175	240	245	2
Illinois 6		Agglom	51.7	10.3	1.195	12.60	12410	100	200	360	330	3
Illinois 6		Agglom	51.4	10.3	1.195	12.60	13620	200	190	240	260	3
Up Elk	C	HMS	53.9	12.1	1.081	11.84	1990	500	190	240	240	0.5
Up Elk		HMS	54.6	13.0	1.083	12.88	1640	0	200	250	260	0
Up Elk		HMS	54.5	13.0	1.083	12.88	1770	100	200	250	255	0
Up Elk		HMS	54.5	13.0	1.083	12.88	1800	200	225	270	250	0
Up Elk		HMS	54.4	13.0	1.083	12.88	1850	400	250	300	320	0
Up Elk		HMS	54.3	13.0	1.083	12.88	2040	600	210		450	1.5
Up Elk		HMS	54.3	13.0	1.083	12.88	2200	800	200		435	2
Up Elk		HMS	54.5	9.0	0.933	8.45	2290	0	150	300	335	1
Up Elk		HMS	54.4	9.0	0.933	8.45	2290	100	180	295	275	2
Up Elk		HMS	54.4	9.0	0.933	8.45	2290	200	180	300	285	2
Up Elk		HMS	54.4	9.0	0.933	8.45	2340	400	200	300	300	3
Up Elk		HMS	54.4	9.0	0.933	8.45	2340	400	200	300	300	3
Up Elk	D	HMS/FL	53.9	12.1	1.152	12.22	2530	800	200	310	260	1
Up Elk		HMS/FL	54.6	13.0	1.179	13.24	1800	0	200	270	280	0
Up Elk		HMS/FL	54.6	13.0	1.179	13.24	1990	100	210	280	240	0
Up Elk		HMS/FL	54.5	13.0	1.179	13.24	2070	200	200	300	255	0
Up Elk		HMS/FL	54.5	13.0	1.179	13.24	2210	400	240	255	255	0.5
Up Elk		HMS/FL	54.4	13.0	1.179	13.24	2390	600	210		510	0.5
Up Elk		HMS/FL	54.3	13.0	1.179	13.24	2550	800	190			1.5
Up Elk		HMS/FL	53.9	9.0	0.958	8.49	2700	0	190	330	340	2
Up Elk	E	Chemi	53.5	12.0	1.157	12.54	2300	600	200	355	345	1.5
Up Elk		Chemi	53.7	13.0	1.128	13.18	1660	0	200	265	270	0
Up Elk		Chemi	53.7	13.0	1.128	13.18	1770	100	200	260	260	0
Up Elk		Chemi	53.6	13.0	1.128	13.18	1820	200	210	300	280	0
Up Elk		Chemi	53.6	13.0	1.128	13.18	1980	400	220	380	380	0
Up Elk		Chemi	53.5	13.0	1.128	13.18	1990	600	185			1.5
Up Elk		Chemi	53.4	13.0	1.128	13.18	2220	800	200			2
Up Elk		Chemi	53.8	9.2	1.021	8.93	2850	0	220	480	535	1.5
Up Elk		Chemi	53.7	9.2	1.021	8.93	2980	100	225	450	600	2
Up Elk		Chemi	53.7	9.2	1.021	8.93	3060	200	275	560	530	3
Up Elk		Chemi	53.6	9.2	1.021	8.93	3220	400	200	420	460	3
Up Elk		Chemi	53.6	9.2	1.021	8.93	3220	400	200	420	460	3
Up Elk	G	Flotaf	54.3	11.1	1.116	11.16	2530	0	200	240	240	2.5
Up Elk		Flotaf	54.3	13.0	1.086	13.10	2530	0	210	300	340	2
Up Elk		Flotaf	54.2	13.0	1.086	13.10	2660	100	200	240	2230	2
Up Elk		Flotaf	54.2	13.0	1.086	13.10	2710	200	210	295	315	2
Up Elk		Flotaf	54.1	13.0	1.086	13.10	2900	400	225	280	270	3
Up Elk		Flotaf	53.4	9.9	1.091	10.02	3550	0	200	280	320	2
Up Elk		Flotaf	53.4	9.9	1.091	10.02	3600	100	190	240	240	3
Up Elk		Flotaf	53.3	9.9	1.091	10.02	3650	200	200	260	240	3
Up Elk		Flotaf	53.2	9.9	1.091	10.02	3750	400	200	260	240	3
Up Elk		Flotaf	53.2	9.9	1.091	10.02	3750	400	200	260	240	3

TABLE 4.2
STABILITY RATING
(Volume of Sediment Layer, %)

Stability Rating	Soft-Pack	Medium-Pack	Hard-Pack	Very Hard-Pack
3.0	>90	<10	<5	<5
2.5	any	10-35	<5	<5
2.0	any	>35	<10	<5
1.5	any	any	10-25	<10
1.0	any	any	>25	<10
0.5	any	any	any	10-25
0.0	any	any	any	>25

TABLE 4.3

SUMMARY OF CHEMICAL STABILIZATION 2-MONTH STORAGE TEST RESULTS

Note: Test slurries were blended to have the same nominally minus 45-micrometer top size but have the two different mass mean particle sizes.

	Beneficiation	Amount of Flocon Required, ppm Coal	MMD, μm	Coal in Slurry		Viscosity cP	Mid-Size ^a Weight %	R-R "n" ^b	-2 μm Weight %	Calculated Specific Surface sq m/g
				Weight %	Volume %					
Upper Wyodak	HMS	0	12.6	35.8	43.6	310	41.6	1.002	15.83	1.261
Upper Wyodak	HMS	0	9.0	34.0	41.2	325	28.9	0.856	24.55	1.802
Illinois No. 6	HMS	400	13.0	54.1	51.7	220	46.2	1.0 ^{1/4}	13.06	1.114
Illinois No. 6	HMS	0	8.8	53.1	50.6	200	37.3	0.916	22.85	1.664
Illinois No. 6	Agglomeration	100	10.3	51.7	49.5	200	45.2	1.195	10.66	0.969
Upper Elkhorn	HMS	900 ^c	13.0	54.3	49.8	200	45.2	1.083	11.79	1.047
Upper Elkhorn	HMS	400	9.0	54.5	50.0	200	36.9	0.933	20.02	1.531
Upper Elkhorn	HMS/Filtration	1,000 ^c	13.0	54.3	49.7	190	49.5	1.179	9.90	0.968
Upper Elkhorn	HMS/Filtration	200 ^c	9.0	53.9	49.3	190	34.8	0.958	19.91	1.560
Upper Elkhorn	Chemical	900 ^c	13.0	54.3	50.1	200	46.8	1.128	10.57	0.972
Upper Elkhorn	Chemical	200	9.2	53.7	49.5	275	36.2	1.021	16.46	1.317
Upper Elkhorn	Flotation	400	13.0	54.1	49.7	225	47.0	1.086	11.13	0.997
Upper Elkhorn	Flotation	100	9.9	53.4	49.0	190	42.2	1.091	14.50	1.251

^aWeight % in particle size range approximately 50% of MMD (6 – 20 μm for 13.0 μm MMD and 5 – 15 μm MMD for 9.0 μm MMD coal).

^bSlope parameter in Rosin-Rammler particle size distribution.

^cEstimated amount required to obtain stability rating of 3 instead of 2 or 2.5 after 2 months.

Figure 4.1 Stabilizer Required to Provide 2-Month Stabilization for All Coals

Figure 4.2 Stabilizer Required to Provide 2-Month Stabilization by Source Coal

Figure 4.3 Stabilizer Required to Provide 2-Month Stabilization by Beneficiation Process

Figure 4.4 Stabilizer Required to Provide 2-Month Stabilization versus the Rosin-Rammler Slope Parameter by MMD

Figure 4.5 Stabilizer Required to Provide 2-Month Stabilization versus the Rosin-Rammler Slope Parameter by Source Coal

Figure 4.6 Stabilizer Required to Provide 2-Month Stabilization versus Weight Fraction in Mid-Range by MMD

Figure 4.7 Stabilizer Required to Provide 2-Month Stabilization versus Weight Fraction in Mid-Range by Source Coal

Figure 4.8 Stabilizer Required to Provide 2-Month Stabilization versus Calculated Specific Surface by MMD

Figure 4.9 Stabilizer Required to Provide 2-Month Stabilization versus Calculated Specific Surface by Source Coal

Figure 4.10 Stabilizer Required to Provide 2-Month Stabilization versus Weight Percent Under 2 µm by MMD

Figure 4.11 Stabilizer Required to Provide 2-Month Stabilization versus Weight Percent Under 2 µm by Source Coal

stabilizer required for all the CWFs that were prepared with two (2) MMDs – 9 μm and 13 μm . The CWF with the smaller MMD, 9 μm , had better stability than the 13 μm -MMD CWFs. A comparison of the effect on source coal type can be seen from Figure 4.2. The lower ranked CWFs were inherently more stable. Wyodak, a low ranking subbituminous coal, required no stabilizer at all. The Illinois No. 6, a low ranking bituminous coal, required substantially less stabilizer for its 13 μm -MMD CWF than the Upper Elkhorn fuel and required none for the 9 μm -MMD grind. The effect of the beneficiation process on CWF stability can be seen from Figure 4.3, which is a plot of CWFs made with Upper Elkhorn No. 3 and cleaned by heavy separation, heavy media separation/filtered, chemical cleaning and froth flotation. The 9 μm -MMD CWFs cleaned by froth flotation and heavy media separated/filtered exhibited the best stability. The chemically cleaned CWF required about one half the amount of stabilizer for 2-month stability as that required by the heavy media separated CWF. Figure 4.4 gives a graph of the Flocon required for 2-month stability versus the Rosin-Rammler slope parameter, n . The Rosin-Rammler distribution is described by the following

$$\% \text{ PASSING} = 100 \left[1 - \exp \left(\frac{-x}{k} \right)^n \right]$$

where

x = particle size, μm

n = slope parameter

k = size parameter

The slope parameter, n , indicates the particle size distribution. Low values of n indicate a wider distribution or the presence of more fines. Also, n , is generally similar for materials ground in a similar manner. The size parameter, k , changes depending on the degree of grinding. Figure 4.4 gives the amount of stabilizer needed for 2-month stability versus the Rosin-Rammler slope parameter, n , for the two MMDs that were used – 9 μm and 13 μm . As can be seen in the graph, the lower the slope parameter, n , the more stable the CWF. All the slurries follow this trend except for the CWFs prepared by froth flotation and oil agglomeration. These processes leave residual oil in the CWF which changes their stability characteristics. The wider distribution also implies a more bimodal size distribution. Figure 4.5 shows a similar plot for the three different source coals. Figures 4.6 and 4.7 show the stabilizer (Flocon) needed versus the weight fraction in the mid-range. The mid-range is defined as follows

For 9 μm MMD: 5 μm < mid-range < 15 μm

For 13 μm MMD: 6 μm < mid-range < 20 μm

The calculated specific surface is graphed with the 2-month stabilization required in Figures 4.8 and 4.9 by MMD and coal type, respectively. The figures show that the greater the specific surface, the better the stability. A larger specific area is indicative of smaller particle size. Figures 4.10 and 4.11 are graphs of stabilizer versus the weight percent of particles in the CWF that is under 2 μm . These plots indicate that the larger amounts of fines in the CWF increase their stability.

An effort was made to relate these minimum Flocon requirements to the properties of the coals and slurries by plotting the data in various ways and by regression analyses. The variables considered were weight loading, volume loading, viscosity, particle size distribution (mass mean diameter, weight fraction in mid-size range, calculated specific surface, Rosin-Rammler parameters, amount of minus 2 micrometer fines), coal rank (MAF volatile matter), A-23 dosage, and beneficiation method.

Of the variables considered, the coal rank, particle size distribution parameter, and one of the beneficiation methods showed significant correlation with the amount of Flocon required to form a stable slurry. Slurries made from the beneficiated higher rank Upper Elkhorn coal required larger additions of Flocon than those made from the lower rank coals. The best correlations were obtained when using the mass mean diameter (MMD) as the particle size distribution parameter, and slurries formulated from 13.0- μm MMD coals required more Flocon than slurries formulated from 9.0- μm MMD coals. This is shown in Figure 4.12. Figure 4.12 also shows that slurries prepared from Upper Elkhorn coal cleaned by froth flotation required considerably less Flocon than did comparable slurries prepared from Upper Elkhorn coal cleaned either by HMS (heavy media separation) or chemical procedures. This may be due to the froth reagents added during the beneficiation process, methyl amyl alcohol and No. 2 diesel. It did not appear that the amount of Flocon required when Illinois No. 6 coal was cleaned by the Bechtel agglomeration process was much different from the amount that would be needed if the same coal were cleaned by HMS. A regression analysis of MMD, coal rank (i.e., volatile matter), and beneficiation was done to relate the amount of Flocon needed for 2-month stability. The following algorithm was determined.

$$\begin{aligned} \text{Required Flocon, ppm} = & 597.0(\text{MMD}) - 12.5(\text{MMD})(\text{VM}) - 256.6(\text{VM}) \\ & + 4.18(\text{VM})^2 + 2,719.8 - 415 F (\text{cleaning}) \end{aligned}$$

where:

$F (\text{cleaning}) = 1$ for froth flotation and 0 for the others.

Figure 4.12 Regression Analysis of Stabilizer Required to Obtain 2-Month Stability
(Heavy Lines Show Result of Regression Analysis)

The ranges of coal loading and slurry viscosity observed in the data set were not large enough to allow detection of any influence that these variables might have on the stability of the fuel. The amount of A-23 added to each slurry in order to obtain a nominally 250-cP viscosity was too closely related to the rank of the coal for its effect to be distinguished from the effects of differing coal rank.

4.2 MECHANICAL RESUSPENSION

The mechanical resuspension activities were divided into three parts:

- Investigate periodic agitation for maintaining slurry fuels in good condition.
- Investigate the effects of storage tank configuration on the ease of remixing the slurry fuel.
- Develop a recycling pumping strategy.

The basic parameters defined by these activities were used to design a specific program for comparing and optimizing the resuspension characteristics of slurries prepared from the various beneficiated coals.

4.2.1 Periodic Agitation

The first part of the mechanical resuspension task was to investigate a periodic agitation strategy for maintaining slurry fuels in good condition for use. Eight slurries were selected from those left from the chemical storage testing to represent those that settled to a hard-pack condition in one month (Type A) and those that settled to a medium-pack condition in one month (Type B). Four of the slurries contained Flocon and four did not. The individual remixing experiments were on 1-liter splits of the slurries stored in wide-mouth screw-cap plastic bottles. A laboratory stirrer with a three-blade propeller was used for remixing the samples (at 540 rpm).

The objective of these experiments was to determine whether the amount of residual hard-pack and very hard-pack sediment remaining after frequent and infrequent remixing schedules would increase with time over a 2-month storage period. A further objective was to determine whether frequent or infrequent remixing would have an effect on the rheology of the slurries.

The remixing schedules varied according to the previously observed stability of the slurries as follows:

Slurry	Remixing, Times per Month			
	Frequent	Intermediate	Infrequent	Control
Type A	21 ^a	4	2	0
Type B	8 ^b	4	1	0

^a5 per week.

^b2 per week.

The mixer blade position and mixing time were selected for the first remixing of each schedule so that the blade would clear any hard-pack sediment and suspend essentially all of the cake from the bottom of the container. Whenever possible, the same blade position and stirring time were used for subsequent remixings. In a few cases, it was necessary to raise the blade or extend the stirring time in order to adequately remix a sample. Six blade position/stirring time configurations were possible, as follows:

Configuration	Position, Inches from Bottom	Stirring Time, Minutes
0	Control, No Mixing	
1	1	1
2	1-1/2	1
3	2	3
4	3	4
5	3-1/2	12

The samples were probed after remixing and the thicknesses of the various consistencies of cake were recorded. These results are summarized in the tables in Appendix A. The depths of the combined hard-pack and very hard-pack cakes accumulated in the eight slurries after a 2-month exposure to the various remixing frequencies are charted in Appendix B. Cake depths are shown as percentages of the total slurry depth in the figures, and if the slurries were not remixing during storage, the combined hard-pack and very hard-pack sediments accounted for between 20 and 80 percent of the total slurry volume of these samples. In all cases, a weekly or more frequent remixing schedule (more than 4 times per month) reduced the sediment accumulation to less than 5 percent of the slurry volume, and for 6 of the 8 slurries, a biweekly or monthly remixing schedule would have accomplished the same result. There was only one case (Figure B.8) in which frequent remixing (8 or more times per month) rather than infrequent remixing resulted in the accumulation of more rather than less sediment.

Brief statistical tests were made on the storage data to determine whether cake accumulations could be correlated with slurry properties. One pattern found to be significant was a small increase in the accumulation of sediment with an increasing amount of Flocon in the slurry formulation. This is shown in Figure 4.13 for the Upper Elkhorn slurry samples which were remixed weekly. The pattern shown in Figure 4.13 may not be a true cause-and-effect relationship, however, since more Flocon may have been used in certain slurries than in others in order to overcome these same settling tendencies. Figure 4.13 also shows that the slurry prepared from Upper Elkhorn coal beneficiated by froth flotation was completely resuspended by a weekly remixing schedule, whereas sediment accumulated in slurries prepared from Upper Elkhorn coal beneficiated by the HMS, HMS/filtration, and chemical procedures.

The viscosities of selected samples were also determined at the conclusion of the 2-month program and are reported in Table 4.4. Most of the slurry samples had somewhat dilatant rheology over the shear rates investigated ($<1000 \text{ s}^{-1}$). The average of the viscosities of the four samples which did not contain Flocon is plotted versus shear rate in Figure 4.14, and the average of the viscosities of the four which did contain Flocon is plotted versus shear rate in Figure 4.15. In both cases, remixing seemed to reduce the apparent viscosity of the slurry, and the effect seemed to be more pronounced for the samples that contained Flocon. The reduction in viscosity amounted to about 15 percent for the latter set of measurements on slurries which had been remixed frequently.

4.2.2 Storage Tank Configuration

The second part of Task 3.2 was also completed. Part 2 was to determine a preferred configuration for fuel storage/mixing tanks and specifically for the tanks to be used for the scheduled comparisons among the seven batches of fuel prepared from beneficiated coals. The principal strategy considered assumed periodic resuspension with a mechanical stirring mixer, but slow-speed continuous mixing, air sparging, and recycle pumping alternatives were also studied.

These tests were done on 35- to 39-gallon lots of slurry, and the mechanical remixing configuration parameters were the following:

- Flat bottom and conical bottom tanks.
- Zero, two, and four baffles in the tank.
- Remixing at 245 and at 410 to 445 rpm.

Figure 4.13 Sediment Accumulated in Slurries Prepared from Beneficiated Upper Elkhorn Coal After 2 Months of a Weekly Remixing Schedule

TABLE 4.4
VISCOSITIES OF SELECTED SLURRIES AFTER 2 MONTHS OF PERIODIC REMIXING

		Viscosity, Centipoise		
Frequency of Remixing	Time per Month	100 s ⁻¹ Shear Rate	500 s ⁻¹ Shear Rate	1,000 s ⁻¹ Shear Rate
Upper Elkhorn HMS Coal, 13.0 μm MMD, 0.34% A-23, 0.04% Flocon				
No Remixing	0	360	480	500
Infrequent	2	260	390	410
Frequent	21	270	410	445
Upper Elkhorn HMS Coal, 9.0 μm MMD, 0.42% A-23, No Flocon				
No Remixing	0	100	340	475
Infrequent	1	105	345	475
Frequent	8	100	285	410
Upper Elkhorn HMS/Filtered Coal, 13.0 μm MMD, 0.405% A-23, 0.04% Flocon				
No Remixing	0	300	480	545
Infrequent	2	250	440	485
Frequent	21	240	400	465
Upper Elkhorn HMS/Filtered Coal, 13.0 μm MMD, 0.47% A-23, 0.08% Flocon				
No Remixing	0	280	460	520
Infrequent	1	285	415	460
Frequent	8	280	400	460
Upper Elkhorn Chemical Coal, 13.0 μm MMD, 0.34% A-23, 0.02% Flocon				
No Remixing	0	400	535	540
Infrequent	2	400	535	540
Frequent	21	300	465	480
Upper Elkhorn Chemical Coal, 9.2 μm MMD, 0.53% A-23, No Flocon				
No Remixing	0	200	580	765
Infrequent	1	185	550	740
Frequent	8	130	540	720
Illinois No. 6 HMS Coal, 13.0 μm MMD, 0.72% A-23, No Flocon				
No Remixing	0	480	440	450
Infrequent	1	480	435	440
Frequent	8	400	395	410
Upper Elkhorn Flotation Coal, 13.0 μm MMD, 0.466% A-23, No Flocon				
No Remixing	0	290	400	430
Infrequent	1	290	380	400
Frequent	8	290	385	410

Figure 4.14 Average Viscosities of Four Sample Slurries Which Did Not Contain Flocon

Figure 4.15 Average Viscosities of Four Samples Which Did Contain Flocon

The flat bottom and cone bottom tanks both had the same kind of ship-propeller-type mixer. Two types of slurry were used for the Part 2 comparisons - one prepared from HMS cleaned Upper Elkhorn coal and the other from chemically cleaned Upper Elkhorn coal. These slurries were selected because they were known to settle rather rapidly so testing could be accomplished in the shortest time.

The resuspension tests were made after the slurries had settled either overnight or over a weekend, and depending on the type of slurry and the settling time, the cake thickness of the sediments ranged between 0.9 and 5.5 inches. This amount of hard-pack or very hard-pack cake filled between 4 and 23 percent of the total depth of the slurry in the tank. The primary measured response was the length of time required for the mixer to fully resuspend the cake. The observed times ranged between 3.5 and 51 minutes. The current drawn by the mixer motors was also recorded so estimates could be made of the power draft and the amount of energy required to resuspend the sediment. These data are presented in Table 4.5.

The data in Table 4.5 were evaluated by averaging all test results for a specific condition. For example, all of the test results for sedimentation in a flat bottom tank were averaged, and the average compared to the average for all of the results for sedimentation in the cone bottom tank. The averages are presented in Table 4.6.

The summarized data in Table 4.6 show that both slurries, one with a poor stability rating and the other with a fair stability rating, required about the same amount of power for remixing. A much longer mixing time was needed, though, to resuspend the thicker cake from the slurry with the poor stability rating, so the energy consumption was much greater, even after adjustment for the differing thickness of the cake. On the other hand, increasing the speed of the mixer increased the power draft significantly, but the mixing time was reduced, so the energy consumption per inch of cake was little changed. Similarly, the data in Table 4.5 show that baffling and a flat bottom improved the effectiveness of the remixing.

The observations described above indicate that a flat bottom tank with four baffles is the preferred configuration when following a periodic remixing strategy. The mixer speed is relatively unimportant except that it might be less expensive to install a lower horsepower medium-speed mixer rather than a higher speed mixer.

Continuous slow-speed mixing was also investigated as a method for dealing with the natural tendency of coal slurries to separate. The same slurries, tanks, and mixers were used as for the periodic resuspension work described above.

TABLE 4.5
RESULTS OF MIXING TESTS FOR RESUSPENSION OF SEDIMENT

Slurry ^a	Configuration				Standing Time, Hours	Sediment Depth, Inches	Remixing			
	Tank ^b	No. of Baffles	Mixer ^c	Mixer, rpm			Estimated hp	Time, Minutes	Hp-hr/1,000 Gallons	Hp-hr/1,000 Gallons/Inch Sediment
A	F	0	1	245	17.5	2.0	0.123	35.00	1.844	0.92
A	F	0	1	445	17.5	2.0	0.361	14.25	2.196	1.10
A	F	2	1	245	17.5	2.0	0.132	10.00	0.566	0.28
A	F	2	1	445	17.5	2.0	0.361	10.00	1.541	0.77
A	F	4	1	245	17.5	2.0	0.132	9.50	0.538	0.27
A	F	4	1	445	17.5	2.0	0.370	8.00	1.264	0.63
A	F	4	1	445	65.5	4.5	0.370	11.50	1.818	0.40
B	C	0	2	245	17.5	0.9	0.121	10.00	0.575	0.66
B	C	0	2	445	17.5	0.9	0.372	5.25	0.930	1.06
B	C	2	2	245	17.5	0.9	0.130	5.75	0.357	0.41
B	C	2	2	445	17.5	0.9	0.382	4.50	0.818	0.93
B	C	4	2	245	17.5	0.9	0.130	4.25	0.264	0.30
B	C	4	2	445	17.5	0.9	0.391	3.50	0.652	0.75
B	C	4	2	245	65.5	2.5	0.130	9.25	0.574	0.23
A	C	0	1	245	17.5	2.0	0.205	51.00	4.478	2.24
A	C	0	1	410	17.5	2.0	0.370	19.00	3.003	1.50
A	C	2	1	245	17.5	2.0	0.205	25.00	2.195	1.10
A	C	2	1	410	17.5	2.0	0.370	15.50	2.450	1.23
A	C	4	1	245	17.5	2.0	0.215	26.50	2.430	1.22
A	C	4	1	410	17.5	2.0	0.370	15.00	2.371	1.19
A	C	4	1	410	65.5	5.5	0.205	27.00	2.371	0.43
A	C	4	1	410	65.5	5.5	0.370	18.00	2.845	0.52
B	F	0	2	245	17.5	0.9	0.217	6.75	0.699	0.80
B	F	0	2	410	17.5	0.9	0.391	4.75	0.885	1.01
B	F	2	2	245	17.5	0.9	0.217	4.50	0.466	0.53
B	F	2	2	410	17.5	0.9	0.391	2.00	0.372	0.43
B	F	4	2	245	17.5	0.9	0.237	3.00	0.338	0.39
B	F	4	2	410	17.5	0.9	0.391	1.75	0.326	0.37
B	F	4	2	245	65.5	1.5	0.227	5.50	0.595	0.40
B	F	4	2	410	65.5	1.5	0.391	2.25	0.419	0.28

^aType A Slurry = HMS cleaned Upper Elkhorn Coal, 16.3 μ m MMD, 55.0% coal, 250 cP at 100 s⁻¹, stability rating 0.5 at 65.5 hours.

Type B Slurry = Chemically cleaned Upper Elkhorn Coal, 23.6 μ m MMD, 53.8% coal, 190 cP at 100 s⁻¹, stability rating 2.0 at 65.5 hours.

^bTank F = 22.5 inches in diameter, flat bottom.

Tank F = 22.5 inches in diameter, cone bottom with 30-degree slope.

^cTwo 1/3-hp variable-speed mixer drives of the same model number.

Both were equipped with 7-inch diameter ship-propeller-type blades set 7 inches above the bottom of the tanks.

TABLE 4.6
SUMMARIZED RESUSPENSION TEST RESULTS

Average Estimated Power Draft and Energy Consumptions				
Parameter	Operating Horsepower	Horsepower/ 1,000 Gallons	Horsepower- Hours/1,000 Gallons	Horsepower-Hours/ 1,000 Gallons/ Inch of Cake
Slurry Stability				
A. Poor	0.28	7.1	2.13	0.92
B. Fair	0.28	7.9	0.55	0.57
Mixer Speed				
245 rpm	0.17	4.7	1.14	0.70
410 – 445 rpm	0.37	9.9	1.52	0.79
Baffles				
None	0.27	7.3	1.83	1.16
2	0.27	7.4	1.10	0.71
4	0.28	7.6	1.02	0.63
Tank Bottom				
Flat	0.27	7.2	0.92	0.57
Cone	0.26	7.1	1.75	0.92

In this case, the measured response was the minimum mixer speed which prevented formation of a hard-pack sediment over a 17.5-hour period. The following observations were made:

Slurry	Tank Bottom	Baffles	Minimum rpm	Estimated Horsepower
A. Poor Stability	Cone	0	60	0.04
A. Poor Stability	Cone	4	90	0.05
B. Fair Stability	Flat	0	75	0.04
B. Fair Stability	Flat	4	90	0.05

The preferred tank configuration for a continuous agitation strategy appears to be different from the preferred configuration for periodic remixing strategy. It appears, for instance, that baffles impede the formation of vortex flow patterns which sweep sediment from the bottom of the tank during slow speed mixing. Also, a conical bottom appears to aid development of the favorable flow patterns for holding the coal in suspension. Power requirements are quite low (on the order of 1.8 hp per 1,000 gallons), but energy would be consumed around the clock rather than periodically.

4.2.3 Recycling Pumping Strategy

Pump recycling was next evaluated as an alternative method for preventing sedimentation. Two entry flow patterns and two flow rates were tried. The following data were obtained for the Type A poor stability slurry:

Entry Flow Pattern	Flow Rate, gpm	Turnover Ratio Tank, Volumes/Hour	Duration, Hours	Sediment, Inches
Vertical	4 to 5	6 to 8	1	0.50
Tangential	4 to 5	6 to 8	1	<0.25
Tangential	5 to 6	8 to 9	17.5	0.62
Tangential	5 to 6	8 to 9	72	2.75

It appears from these data that exceedingly high pumping rates are necessary to hold coal slurry in suspension (over at least 150 gpm per 1,000 gallons).

Recycle pumping was also attempted with the Type B fair-stability slurry, but a pump failure occurred and a portion of the slurry was lost.

Continuous and periodic air lifting and sparging were investigated as alternatives to mechanical mixers. No sediment buildup was seen during a 17.5-hour test with a continuous air flow, estimated at 60 cfm and 5 psi, from the bottom of the cone bottom tank. The change in slurry volume due to evaporation of water was monitored during this test, and the loss did not appear to be any greater than losses observed during mechanical mixing.

The time required to resuspend caked sediment by air sparging was also determined. These tests were done in the flat bottom tank using the Type B fair-stability slurry. Two configurations were used. In one configuration, the air inlet was at a fixed position through the bottom at the center line of the tank. A 1/2-inch pipe air lance was used from above in the other configuration, and the operator moved the tip as needed to break up and resuspend the cake. In both cases, the air flow was estimated to be approximately 80 cfm at 10 psi. The following data were gathered:

Configuration of Air Inlet	Settling Time, Hours	Cake, Inches	Time Needed to Resuspend	
			Minutes	Minutes/Inch Cake
Moving Lance	120	3.5	65	19
Moving Lance	17.5	1.5	21.5	14
Center Fixed	17.5	1.5	55 ^a	37 ^a
Center Fixed	17.5	1.5	85 ^b	57 ^b

^aAll but 1/4 inch of sediment at circumference of tank.

^bCake completely resuspended.

These data show the effectiveness of air lancing as a method for breaking up and resuspending coal slurry sediment. A movable lance approach is quite labor-intensive, but the same effect can be obtained by multiple air entry points at the bottom of the tank. The inlets can be no farther apart than 22 inches to match the results of the center fixed inlet configuration listed above and need to be more closely spaced to match the results of the moving lance approach.

Water was added to the slurries as needed to replace the volume lost due to evaporation. Properties of the slurries were measured at the conclusion of the resuspension work for comparison with the original slurry. The properties of the slurry were found to have changed minimally.

5. RESIDENTIAL STORAGE

In order to effectively store CWFs at a residential site several issues were addressed. They included slurry stability, tank design, mechanical resuspension, and effects of freeze/thaw cycles. The CWF stability and mechanical resuspension test results found under bulk storage (Section 4) can be directly applied to residential storage.

The major consideration is the intermittent duty cycle that a CWF furnace would have in a residence. The frequency of on time for the CWF furnace varies markedly during the heating season as compared with the furnace time during the off-season. The handling system must be able to tolerate these irregular cycles along with being immune to the properties of the CWF. This is a requirement to ensure optimal performance of the CWF furnace at all times.

5.1 TANK DESIGN

The frequency of resuspension required can be determined by two methods - a knowledge of the slurry stability characteristics or a dynamic measurement of slurry settling. Stability data obtained from tests can determine the minimum amount of time that the slurries considered for use in the system can be stored before resuspension can begin. A control system with a simple timer can actuate the mixing system at the appropriate time. Stability tests have shown that all the CWFs examined can achieve a 2-month stability. However, it is expected that the 2-month period may be exceeded during warmer weather.

Several sensors were investigated for use as a measurement approach to slurry settling. Settling of the slurry in the tank is the movement of coal particles to the bottom of the tank creating a nonhomogeneous suspension. The stratification of coal particles within the tank can be translated to density difference of the slurry within the tank. A sensor could be used to measure density changes within the tank. A mechanical type density sensor using moving floats would be unacceptable in a slurry environment. The feasibility of using ultrasonic, vibrating probe, and pressure transducers was studied. Panametric Inc. is currently testing a settling sensor using an ultrasonic device. Other sensor manufacturers are being contacted.

An experimental test rig was used to test the sensors. All the sensors were mounted to a 55-gallon drum that contained CWF (Upper Elkhorn No. 3 HMS/Filtered). As the slurry settled each sensor would emit a signal indicating settling.

By continually monitoring the status of the CWF suspension, mixing can be initiated at the appropriate time. This can reduce the use of the mixing system and minimize both the electrical power consumption and the mechanical work into the CWF.

The vibrating probe sensor consists of a vibration transducer and a radio frequency (RF) capacitance transducer to determine slurry settling. The unit works through a low-voltage, crystal-controlled oscillator applied to an inductor capacitor (L-C) circuit which includes the probe capacitance. Changes in the probe capacitance or impedance caused a change in the phase relationship of the L-C circuit. The unit (Monitrol Model Number PK21WP) is generally used as a level switch in tanks containing solids. The probe is driven to vibrate at its resonant frequency by an amplified feedback circuit. The presence of a substance (e.g., coal water slurry) on the probe is detected as a voltage change in the circuit.

Tests showed that the vibrating probe sensor could only detect significant change in the condition of the CWF. Although the instrument was set to its highest sensitivity, the CWF formed a soft-pack before the vibrating probe detected settling. It was concluded that the instrument in its present form could not be used to detect CWF settling.

Another method that was tested to sense the settling of CWF was with a differential pressure transmitter. By measuring the change in pressure near the bottom of the tank, the onset of settling could be detected. Initially, a pressure reading is taken when the CWF has been mixed and used as a reference. As the CWF settles the pressure difference increases, indicating an increase in density. Laboratory testing found that the lines connecting the transducer to the tank repeatedly clogged. In order for this method to work practically, a flush-mounted set of transducers mounted to the tank wall would eliminate the problem of plugged lines.

The use of sound waves to determine settling in CWFs was also investigated. A Panametrics Model 6468 Ultrasonic Flowmeter control unit was used to monitor signal quality and amplitude from the transducers. This system is typically used to measure the velocity in pipe flow. Transducers are generally mounted externally to the pipe. Initially, tests were conducted by mounting the transducers externally on a storage tank containing CWF. Difficulties were encountered with sound being transmitted through the tank walls. A set of submersible transducers were fabricated and placed in the tank. The faces of the transducers were separated by 5 inches by mounting them in a jig. Results are shown in Figure 5.1. For over 45 hours the speed of sound of the CWF remained constant. After this there was a steady increase until the sediment formed became a soft-pack. The speed of sound for water (4,890 ft/s) is also given in the plot. As can be expected because of the higher density, the CWF (Sp. Gr. 1.15) has a higher speed of sound.

Figure 5.1 Ultrasonic Sensor Results

The design of a storage system for CWF must address the drying characteristics of slurry on coated surfaces. As the level of the slurry in the tank decreases the wetted surfaces dry out. Repeated coatings of slurry cake up and produce thick layers of dry slurry that could flake off into the slurry, creating blockage problems in the pumping loop. Since this is a small-scale system, small-diameter pipe is a prerequisite to maintain a high enough velocity to prevent settling of the particles within the pipe network.

Several tank designs were investigated. Some of the tank design criteria overlap the design considerations for slurry resuspension. One concept that was tested utilized a collapsible bladder. The bladder was filled with slurry and was constrained within a solid enclosure. The inlet was at the top and the outlet was at the bottom of the bladder. As slurry was removed the bladder collapsed and prevented drying of the CWF. A bench-scale prototype was built and tested. Initial tests with water showed good results; however, the bag ruptured when it was used with CWF. The bag was made of a rubber material which actually stretched during filling. This caused stresses in the skin. An alternate material, polyurethane, was successfully tested. The polyurethane easily conformed itself to the contours of the tank thereby supporting the weight of the CWF.

Another tank design using humidification above the free surface of the slurry would prevent drying of the slurry on the internal walls. This would prevent moisture from evaporating from the slurry into the air pocket above the slurry surface, which would dry the slurry. Small-scale experiments were conducted to demonstrate the humidification concept. Tests results showed that humidification did prevent caking of slurry on the tank walls. In fact a tank was repeatedly coated with CWF and allowed to dry. After humidification the dry CWF on the walls was reconstituted and would not create a threat to blocking the transfer line.

5.2 STORAGE AND HANDLING SYSTEM

A storage and handling system, shown in Figure 5.2, was constructed and tested. A diagram of the system is given in Figure 5.3. The system is divided into two areas: the storage facility and the combustor. Typically, the distance between them will be 10 to 20 feet at a residential site.

The following gives an explanation of the handling/storage system operation. A three-way valve at the bottom of the tank diverts the flow from the slurry tank or the flushing tank to the pump. When slurry is to be delivered to the combustor, the slurry flows through the strainer, pump, then through an accumulator, and then to the atomizer. The accumulator is used to dampen the flow pulsations due to the peristaltic pump. During shutdown, the pump is deactivated and a short burst of water is used to flush the atomizer, which would quickly get plugged from slurry

Figure 5.2 Photograph of Storage and Handling System

Figure 5.3 Residential Slurry Storage and Handling System

due to residual heat in the combustor drying the slurry. The slurry in the lines can remain there for some time before the lines have to be flushed. After an allotted time (approximately 12 hours), the lines are flushed. The valve is diverted to bring water from the flushing tank through the pump and flush the lines through valve 4 and then back to the flushing tank. Then the pump is reversed to empty the line of water so that at startup excess amounts of water do not enter the combustor. The storage facility was successfully tested demonstrating its practical application to residential storage and handling of CWF. The valves in the system were made of different materials - PVC, brass, and stainless steel. Most of the valves were pneumatically actuated. Since an air compressor is required for the fuel atomizer in the CWF furnace system, compressed air would be available at the residential site. During the course of testing no failures of these components occurred.

5.3 CLIMATIC ASSESSMENT

Temperature is the only climatic condition that can really affect a CWF since the slurry is always contained. Variations in atmospheric pressure are too small to be of importance, and changes in humidity or other climatic conditions have no direct impact on the contained fuel.

The effect of temperature (including freeze-thaw cycles) on stability of CWFs has been investigated by others. Tests were conducted by the Adelphi Center for Energy Studies on CWFs supplied by four producers. Static stability was measured after the fuel was stored at temperatures of 2°C, 20°C, and 48.9°C. Stability was measured initially and at intervals of one hour, one day, two days, three days, and seven days. In addition, freeze-thaw tests were performed. For these tests the samples were stored at -16°C for 16 hours and then thawed at 20°C for 8 hours. This freeze-thaw cycle was repeated three times, with measurements before and after each cycle. Excellent stability was observed at 20°C for the majority of samples, but a drop in stability occurred at elevated temperatures. At 2°C, half the samples were stable and half showed decreased stability. Only one sample from the freeze-thaw testing showed decreased stability. Eight slurries were tested for viscosity after the freeze-thaw cycling. One sample showed a 22-percent decrease in viscosity, two showed little change, and the others all increased in viscosity.

In freeze-thaw tests reported by Batra and Kenney, a 68-percent-wt. CWF was frozen for 12 hours and thawed for one hour. The sample was checked for both stability and rheological characteristics after mixing. No coal settling was observed in the process, and the fuel exhibited excellent stability during the freeze-thaw process. In viscosity tests after the freeze-thaw process, the sample exhibited a higher viscosity than before freezing, but the shapes of the viscosity-shear rate curves were very similar.

In the present work the affect of freeze-thaw cycles on CWF was to be tested on the seven (7) CWFs that were prepared. The testing procedure began by taking baseline particle size measurements and viscosity measurements for the CWFs. All seven CWFs were frozen in quart containers. After a single freeze-thaw cycle the slurry did not return to its original state. Once the slurries were thawed, very little free flowing liquid was observed in the containers, particularly with some of the slurries (Illinois No. 6 - HMS, Wyodak - HMS, Illinois No. 6 - Oil Agglomeration, and Upper Elkhorn No. 3 - Froth Flotation). The slurries retained a heavy paste-like consistency until they were agitated and returned to a liquid consistency. Attempts to measure particle size distribution were abandoned due to large agglomerated particles that could not easily be broken apart with normal agitation. If a large tank of slurry was allowed to freeze, a large amount of energy would be required to return the slurry to a liquid consistency and even then would contain agglomerated particles.

Additional freeze-thaw tests were conducted to determine the implication of freezing the slurries in tubes. Two foot-long sections of polyethylene tubing were filled with the CWFs and then frozen. They were allowed to thaw and were then connected to a pump. The CWF pushed through the tubing was of a paste-like consistency similar to that used in the tests conducted in the containers. This would be unacceptable in an actual handling system. A control sample with CWF that was not frozen flowed easily.

From the tests results obtained it is recommended that the CWF not be allowed to freeze during any stage of preparation, transport, or storage. An insulated tank with wall heaters should be used to prevent freezing during bulk storage. Delivery trucks would possibly need to be insulated. The tanker trucks may need to be garaged or fitted with wall heaters during stagnant night hours. During the daytime no special precautions may be needed other than insulating the tank on the truck because of the size and time needed for the heat in the slurry to be conducted to the tank wall. Once the fuel is delivered to the residence, it will be stored indoors where it will not be exposed to extreme temperature changes.

6. RESIDENTIAL HANDLING (TASK 5)

The required piping network used in a small-scale residential CWF furnace installation has several unique requirements. The system should be able to meter a highly viscous non-Newtonian fluid (CWF) to the atomizer in the combustor and flush the atomizer to prevent clogging. The work performed in this task identifies relevant issues in slurry handling for a residential application and builds a database for the design of such a system.

6.1 PUMP EVALUATION

Slurry pump operating criteria for transfer to the atomizer and resuspension requirements are quite different. The pump required to transport the slurry from the tank to the atomizer in the combustor must be capable of accurately metering the flow rate to maintain the desired input rate. Generally, a pump that imparts low shear stresses on the slurry is desirable. These include peristaltic, progressing cavity, and diaphragm pumps.

The three different types of pumps were set up into individual flow loops. Each pump recirculated CWF into a tank continuously until a failure occurred.

The diaphragm pump operated for 65 hours before it plugged up. The ball check valves on the inlet and outlet agglomerated coal particles and stopped working. Slurry trapped in the diaphragm cavity dried out after the valves became dysfunctional. The system was cleaned and reactivated several times but the blockage reoccurred.

The progressive cavity pump was operated for about 550 hours. Upon inspection it was found that the stator and rotor suffered excessive wear.

The peristaltic pump failed after 2,280 hours of operation. A cut was created in the axial direction of the tubing within the pump head. The failure caused slurry to fill the pump head and dry out. This caused the rotor to seize and the motor to fail.

In order to determine the life requirement of the components used in CWF systems, the operating hours of a typical residential heating system can be used. The heating degree days for the major cities in the United States fall well below 8000 heating degree days. Therefore, using the assumption that the residential heat load is about 700 Btu/hr-°F (UA product) the total annual energy consumption is 134.4 million Btu. Using a residential heating system size of 100,000 Btu/hr and an efficiency of 80 percent, the annual operating time is

1680 hours. This falls below the operating time obtained for the peristaltic pump before failure. The replacement of the tube within the peristaltic pump can be an annual maintenance item. The cost of the one foot of tubing required is less than \$1.

6.2 TRANSFER LINE EVALUATION

A database giving the flow characteristics of different diameter piping, assorted fittings, and alternate materials was needed to design piping networks that handle the beneficiated CWFs. Since behavior for small-scale applications was nonexistent in literature, the experimental setup was designed to cover a wide variety of sizes and fittings. It was expected that from the test results, one or more of the transfer line sizes could be ruled out for use. However, the data obtained from the larger sized lines (3/4 inch and 1 1/2 inch), which exhibited extremely low shear rates, could be used to further characterize the CWFs.

A test loop containing standard radius elbows, long radius elbows, and straight lengths of pipe (3/8-inch and 3/4-inch diameter) was used to obtain pressure drop characteristics as a function of flow rate. A length of 1 1/2 inch diameter tubing was also in the loop.

The experiments were done to determine the effects of coal/water slurry properties on the performance characteristics of the transfer line. The peristaltic pump was calibrated for the transfer line evaluation. The mass flow rate was measured as a function of pump setting for an Upper Elkhorn and an Illinois No. 6 CWF and was divided by their respective densities to get the volumetric flow rates shown in Figure 6.1. It can be seen from these two measurements that the flow rate was directly proportional to the pump setting and independent of CWF type. Pressure drops were measured on the various elements of the transfer line.

The theoretical treatment of the effects on shear rate of non-Newtonian fluid properties has been derived elsewhere.⁴⁸ The pressure drop in straight pipe sections is the result of the shear stress exerted on the fluid. The shear stress can be found from the following equation to be:

$$\tau_w = \frac{-R}{2} \left(\frac{dP}{dx} \right)$$

where:

τ_w = shear stress

R = tube internal radius

dP/dx = pressure drop per unit length of pipe

TF59-790

Figure 6.1 Volumetric Flow Rate of Two Slurries versus Setting on the Peristaltic Pump Used in the Transfer Line Evaluation

which is independent of fluid properties.

The shear rate must be modified to take into account the effects of non-Newtonian fluid properties. The Rabinowitsch equation modifies the apparent shear rate to correct for the deviation:

$$-\dot{\gamma}_w = \frac{4 Q}{\pi R^3} \left[\frac{3}{4} + \frac{1}{4} \frac{d \ln Q}{d \ln \tau_w} \right]$$

where:

- $-\dot{\gamma}_w$ = shear rate at the wall
- Q = volumetric flow rate
- R = tube internal diameter
- τ_w = shear stress at the tube wall

For a fluid that obeys a power-law equation the differential part of the equation can be reduced to:

$$\frac{d \ln Q}{d \ln \tau_w} = \frac{1}{n}$$

The viscosity was obtained from the transfer line measurements using the ratio of shear stress to shear rate. The plots in Figures 6.2 through 6.8 give data obtained with data from the transfer line at low shear rates and from a rotary-type viscometer at intermediate shear rates.

In the shear rate range under 1,000 1/s the CWFs' behavior is pseudoplastic ($n < 1$), newtonian ($n = 1$), and dilatant ($n > 1$). A capillary viscometer was used to determine the viscosity at shear rates normally encountered during atomization (10^5 sec^{-1}). This will be discussed in Section 6.3.

Additional transfer line measurements were made to determine the effects of different tube materials on pumping with CWF. Each length of material was tested separately. Upper Elkhorn No.3 - heavy media separated CWF was pumped through each 3/8-inch-diameter tube made of different materials (copper, stainless steel, iron, Teflon, and polyethylene), and the pressure drop was measured. The viscosity of the CWF pumped into the tubes was adjusted using Flocon to obtain a viscosity of 150 cP at 80 1/s. Therefore, the use of the CWF with the same initial viscosity characteristics was assured. Figure 6.9 gives a plot of shear stress versus shear rate for each of the tube materials. In general, the points lie about the same line which describes the slurry characteristics. It can be

Figure 6.2 Illinois No. 6 - Heavy Media Separated

Figure 6.3 Wyodak - HMS

Figure 6.4 Upper Elkhorn HMS

Figure 6.5 Upper Elkhorn HMS, Filtered and Washed

Figure 6.6 Upper Elkhorn - Chemically Cleaned

Figure 6.7 Upper Elkhorn No. 3 - Froth Flotation

Figure 6.8 Illinois No. 6 - Oil Agglomeration

FUEL: UPPER ELKHORN, HMS

Figure 6.9 Investigation of Alternate Materials

concluded that the material does not have an effect on the shear stress (i.e., pressure drop). There was some variation in the shear rates in tubes due to slightly different inside diameters.

The pressure drop per unit length of the 3/8 inch straight line, 3/8 inch long radius elbow and 3/8 inch standard elbow versus flow rate for slurries A, C, D, and E are given in Figures 6.10, 6.11, 6.12, and 6.13, respectively. As can be seen from the plot, the pressure drop per unit length for the fittings and the straight section are about the same. As the flow rate increases, the deviation of the fitting pressure drops become larger, indicating that there may be some slight secondary flow effects. However, the entire transfer line could be treated as straight tubing.

Some transfer line measurements were retested to determine the repeatability of the data. In addition, measurements on a Brookfield viscometer were made to verify the results from the transfer line. Variations in the pressure drop from the original measurements were found. However, the viscometer measurements corresponded to the values obtained from the transfer line measurements. This showed that there had been some change in the slurry viscosity. It was determined the stabilizer (Flocon), a xanthum gum, underwent biological degradation. Loss of stabilizer results in a loss of viscosity and stability.

6.3 CAPILLARY VISCOMETRY

The atomization quality of coal water slurry is an important factor in determining the combustion characteristics. It is well known that the viscosity of the slurry at high shear rates has a dominant effect on the size distribution of the atomized fuel droplets. The shear rates under atomization conditions are on the order of 10^5 sec^{-1} . A capillary viscometer is being constructed to measure the viscosity of the beneficiated CWFs at these high shear rates.

The experimental setup shown in Figure 6.14 consists of a cylindrical vessel 4 ft long and 2 in. in diameter. It was designed to operate at a maximum pressure of 1500 psi. One end of the vessel is connected to a nitrogen bottle which provides the pressure required to drive the CWF through the capillary tubes. The capillary tubes that were used have a diameter of 0.070 inch. A pressure transducer was located upstream of the tube. The flow rate was measured using a Micro-Motion detector.

In order to determine the apparent viscosity at each shear rate, the pressure drop through two capillary tubes of different lengths was obtained at the same flow rate. The pressure drop of the fully developed flow through the capillary tube was determined by subtracting the pressure drop values for each tube, thereby

Figure 6.10 Batch A - Pressure Drop versus Flow Rate

Figure 6.11 Batch C - Pressure Drop versus Flow Rate

Figure 6.12 Batch D - Pressure Drop versus Flow Rate

Figure 6.13 Batch E - Pressure Drop versus Flow Rate

Figure 6.14 Capillary Viscometer Setup

eliminating the entrance effects. However, it would have been extremely difficult to adjust the flow rate to be the same when measuring the pressure drop in each tube. Therefore, the following approach was taken. The flow rate for various pressures will be taken for each length. A curve fit was done yielding an expression for pressure as a continuous function of the flow rate. Therefore, at a single flow rate (shear rate) the pressure (shear stress) is found and the viscosity determined. The results are included in the rheograms in Figures 6.2 through 6.8.

7. ATOMIZATION

Understanding atomization is a key step in governing, predicting, and optimizing CWF combustion in CWF combustion systems. Atomization characterization tests were carried out at Carnegie-Mellon University. The tests were directed toward comparison and optimization of CWF properties. High-speed photography and laser diffraction techniques were used to provide information about spray characteristics, including drop size distribution, mean and median spray diameters, spray angle, obscuration, spray velocity, and pulsation frequency. In particular this arrangement allows the detection and study of the largest drops and ligaments in the spray that have the greatest detrimental effect on combustion efficiency. In addition, a comparison of slurry droplet distributions with coal grind distribution and combustion information will allow comparison of the various CWF formulations used in the program and optimization of CWF properties.

Figure 7.1 gives a schematic of the apparatus that is being used to measure the atomization characteristics. A pump supplies liquid/slurry to the atomizer. The atomizing air is supplied from the house air system which delivered pressures up to 90 psig. The air passes through a filter, pressure regulator, and flowmeter before it enters the atomizer.

The atomizer sprays into a downward-moving secondary airstream which reduces spray recirculation and fogging of the windows. Room-temperature secondary air enters the top of the spray chamber. The secondary and atomizing airstreams were separated from the CWF spray in a collection tank below the spray chamber. The spray chamber was constructed of four sides of glass to allow good visibility of the atomization.

The atomization characterization tests are being carried out at Carnegie-Mellon University. The tests are being directed toward the comparison and optimization of CWF properties. High-speed photography and laser diffraction techniques are being used to provide information about spray characteristics, including drop size distribution, mean and median spray diameters, spray angle, obscuration, spray velocity, and pulsation frequency. The use of the two complementary techniques will provide particle size information over the range from 5.8 μm to several centimeters. In particular, this arrangement allows the detection and study of the largest drops and ligaments in the spray that have the greatest detrimental effect on combustion efficiency. In addition, a comparison of slurry droplet distributions with coal grind distribution and combustion information will allow comparison of the various CWF formulations used in the program and optimization of CWF properties.

Figure 7.1 Schematic of Experimental Configuration

The slurry travels through a pressure regulator, valve, and flow meter to the top of the spray chamber where it enters the spray chamber. The atomizer is oriented so that it sprays vertically downward in the four-sided, glass-walled spray chamber. After passing through the spray chamber, the slurry accumulates in the collection tank.

The source of atomizing (or primary) air is the house air system, which delivers air at pressures up to 90 psig. The atomizing air passes through a filter, pressure regulator, and flowmeter before it enters the atomizer.

The atomizer sprays into a downward-moving secondary air stream, which reduces spray recirculation and fogging of the windows. Room-temperature secondary air enters the top of the spray chamber. The secondary and atomizing air streams are separated from the slurry spray in a collection tank below the spray chamber.

The spray chamber is constructed of four sides of glass. The lower walls of the spray chamber are fabricated from galvanized sheet metal. The chamber window brackets have been designed to allow easy window replacement and cleaning.

Three different atomizers were tested: Tecogen's design, Delavan-Delta (Part No. 32163-1), and Bete's XA-EF. Tecogen's nozzle, shown in Figure 7.2, is an annular design with CWF flowing in the central tube while atomizing air flows in the annular passageway around the CWF tube. The airstream shears the CWF to an unstable liquid sheet which breaks up into droplets. The shearing of the CWF to a ligament sheet occurs outside the nozzle, so the atomizer is not subject to erosive wear.⁴⁹ To reduce the amount of atomizing air required and improve the relative shear between the air and CWF the air is brought to supersonic velocities through a converging/diverging section.

The Delavan-Delta nozzle, shown in Figure 7.3, works on two principles. Air enters the air/liquid mixing chamber in a tangential manner while liquid is introduced axially. The air shears the liquid stream and breaks it apart. Thereafter, the liquid/airstream impinges upon a pintle plate further breaking the liquid up into droplets. A disadvantage of the pintle plate is that it is prone to erosion over extended periods of use, particularly with CWF, which is quite abrasive.

The Bete nozzle, shown in Figure 7.4, is an externally mixed fan-shaped atomizing nozzle. Liquid is fed axially through the tip and air is provided through

Figure 7.2 Cutaway Drawing of Tecogen's CWF Fuel Atomizer

Figure 7.3 Delavan-Delta Nozzle (Part No. 32163-1)

Figure 7.4 Cutaway of Bete's XA-EF Series

two orifices. The air imparts opposing momentum on the liquid stream making for a flat-shaped atomization pattern.

Shadowgraphs of the Tecogen nozzle for water and for batches A, B, C, and D, are given in Figures 7.5 through 7.9, respectively. As can be seen, batch A atomizes slightly better than batches B, C, and D. These shadowgraphs were taken at a relatively high air/fuel ratio of 3. Shadowgraphs in Figures 7.10 and 7.11 show that good atomization takes place with the Tecogen nozzle at lower air/fuel ratios of 1.4 and 2.0 at the same liquid flow rate, 1.3 gph. Also, at higher liquid flow rates, 2.7 and 4.6 gph, the Tecogen nozzle gives excellent atomization with low air/fuel ratios, shown in Figures 7.12 through 7.15. The atomization at high flow rates with the Tecogen nozzle implies that it can be used for larger CWF combustors and has further upscaling possibilities.

The Tecogen nozzle did not exhibit any clogging tendencies with CWF. However, after the flow through the atomizer is terminated, a droplet is retained on the atomizer tip due the surface tension effects. In a hot combustor environment this droplet would dry out and clog the nozzle tip. However, this situation is easily alleviated by passing a small amount of water through the tip.

The Delavan nozzle shown in Figures 7.16 and 7.17 shows good atomization was achieved at reasonable air/fuel ratios. Operationally, the Delavan nozzle has some peculiarities. Since it works on an internally mixed/impingement concept, the air and liquid pressures must be properly balanced with the mixing chamber. At times the nozzle that was tested underwent some transient behavior before atomization occurred in a steady fashion. Also, when the air was turned off the slurry backed up into the air inlet and caused a blockage in the passage. Therefore, when the Delavan nozzle is not in use, the nozzle should be flushed with water and a small amount of air purged through the system.

The Bete nozzle shadowgraphs are shown in Figures 7.18 and 7.19. Atomization using the Bete nozzle was good; however severe clogging problems were encountered due to the extremely small liquid passage.

Particle size measurements for the batch C CWF were taken for the Tecogen atomizer. The results are shown in Table 7.1. The mean size for water was approximately 16 μm , whereas the Upper Elkhorn-HMS was under the mean size of 200 μm at a location of 7.6 cm from the nozzle tip. The Tecogen solid cone atomizer presents a flat particle size distribution, as shown in Figure 7.20.

Figure 7.5 Tecogen Nozzle - Water
Water Flow Rate = 1.4 ml/sec
Air Pressure = 80 psia
Air/Liquid = 3.0

Figure 7.6 Tecogen Nozzle
Illinois No. 6 - HMS
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 80 psia
Air/Fuel = 3.0

Figure 7.7 Tecogen Nozzle - Wyodak
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 80 psia
Air/Fuel = 3.0

Figure 7.8 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 80 psia
Air/Fuel = 3.0

Figure 7.9 Tecogen Nozzle
Upper Elkhorn - HMS/Filtered
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 80 psia
Air/Fuel = 3.0

TF52-691

Figure 7.10 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 65 psi
Air Fuel = 2.0

TF53-691

Figure 7.11 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 50 psi
Air/Fuel = 1.4

Figure 7.12 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 2.8 ml/sec
Air Pressure = 65 psi
Air/Fuel = 0.9

Figure 7.13 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 4.5 ml/sec
Air Pressure = 35 psi
Air/Fuel = 0.40

Figure 7.14 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 4.5 ml/sec
Air Pressure = 50 psi
Air/Fuel = 0.60

Figure 7.15 Tecogen Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 4.5 ml/sec
Air Pressure = 80 psi
Air/Fuel = 0.80

TF58-691

Figure 7.16 Delavan Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 1.6 ml/sec
Air Pressure = 50 psi
Air/Fuel = 0.9

Figure 7.17 Delavan Nozzle
Upper Elkhorn - HMS
Liquid Flow Rate = 2.46 ml/sec
Air Pressure = 50 psi
Air/Fuel = 0.6

Figure 7.18 Bete Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 2.7 ml/sec
Air Pressure = 22 psi
Air/Fuel = 0.2

TF61-691

Figure 7.19 Bete Nozzle
Upper Elkhorn - HMS
CWF Flow Rate = 1.4 ml/sec
Air Pressure = 14 psi
Air/Fuel = 0.4

TABLE 7.1
PARTICLE SIZE MEASUREMENTS

Nozzle	Liquid	Axial Location (cm)	Liquid Flow Rate (ml/s)	Fuel/Air Mass Ratio	Planar SMD (microns)
A	Water	7.62	1.4	0.3	11.47
A	Water	10.16	1.4	0.3	11.38
A	Slurry C	7.62	1.4	0.3	208.59
A	Slurry C	10.16	1.4	0.3	246.25
A	Slurry C	10.16	0.7	0.3	362.05

Figure 7.20 Droplet Size Distribution of Water from Nozzle A
Water Flow Rate = 1.4 ml/s, $F/A = 0.3$

8. ECONOMIC EVALUATION

An economic evaluation was conducted to determine the viability of using a CWF warm air furnace system in a residential application. The cost basis for the CWF warm furnace and the analysis was established in the program "CWF-Fired Residential Warm-Air Heating System," conducted by Tecogen. The guidelines used for the economic analysis in that program was followed closely since the inclusion of the handling and storage system is a natural extension of the original CWF furnace development program.

A high-volume production cost estimate of the warm air furnace was made in conjunction with a manufacturer, Yukon Energy Inc. The following economic analysis looks at the addition of components necessary to store and handle the CWF in a residence. Figure 8.1 is a drawing of the warm air furnace.

Based on the production of 1,000 units per year, the estimated cost for the furnace was \$3,000. This cost included all the ancillary components needed to supply compressed air to the system and a pump to feed the CWF to the combustor. It was estimated that the handling and storage system shown in Figure 8.2 would cost about \$850. The components were priced in quantities of 1,000. Therefore, the cost of the CWF furnace system including the storage and handling system was \$3,850.

The cost of the CWF furnace system was greater than conventional oil and gas systems. The following economic comparison was done for the CWF and oil systems. It was thought that since both CWF and oil systems require on-site storage this would make a proper comparison. In order to make proper comparisons Total Life-Cycle Cost (TLCC) was used due to the differences in fuel cost.

The cost analysis was done using a standard oil system. A purchase price of \$1,030, AFUE of 80 percent, installation price of \$1,000, and annual maintenance of \$75 were established. The CWF furnace was assumed to have an AFUE of 80 percent, installation cost \$1,000, and an annual maintenance cost of \$100.

Other assumptions made for the economic analysis include a general interest rate of 8.00 percent and a fuel inflation rate of 6.00 percent. The assumptions included heating a home that has an overall heat transfer coefficient surface area product (UA) of 700 Btu/hr-F (for a 1,850 square foot home).

Figure 8.2 Residential Slurry Storage and Handling System

The plot in Figure 8.3 summarizes the economic comparison for the CWF and conventional oil systems. The plot gives the required degree-days for payback versus the differential cost of CWF and oil. Curves for 5-, 10-, 15-, and 20-year paybacks have been included. The payback is dependent on the fuel cost differential and degree-days. Shown in the plot are the degree-days and fuel differential for Pittsburgh and Boston. For Pittsburgh a payback of about 12 years is required. In the case of Boston, the payback period is about 9 years. The figure also includes the degree-days and average annual oil prices for other major U.S. cities.

CWF COST: \$4.79/MMBTU		AVERAGE ANNUAL OIL COST (MAY 1990 TO APRIL 1991)	
		\$/MMBTU	DEGREE DAYS
BOSTON		7.95	5,618
PITTSBURGH		7.30	5,931
CHICAGO		8.29	6,129
DETROIT		8.64	7,443
ST. LOUIS		6.96	4,570
BALTIMORE		8.26	5,035
NEW YORK		8.71	4,847
U.S. AVERAGE		8.10	

Figure 8.3 Economic Comparison

9. CONCLUSIONS AND RECOMMENDATIONS

The relevant issues associated with the storage, handling, and atomization of beneficiated CWFs were examined for small-scale applications. It was found that the issues involved with small-scale systems were the same as those for large-scale systems that have been examined in the past. One exception was pumps. While progressive cavity, lobe-type, and diaphragm pumps performed satisfactorily on a large scale, peristaltic pumps were the only type that worked well for small-scale or low flow rate systems.

A demonstration storage and handling facility was designed and tested and showed practical operation and reliability for use in residential applications. An economic evaluation of the CWF furnace coupled to the storage and handling system gave a payback of 9 and 11 years for Boston and Pittsburgh, respectively.

Seven beneficiated CWFs were prepared. They included three different ranks (bituminous - hvA, bituminous - hvC, and subbituminous - Group C) of coal with five different cleaning processes. Properties approached or exceeded specification for the bituminous coal slurry. Upper Wyodak loading and heating value could not achieve specification. The Illinois No. 6 Fuels had high sulfur content due to high organic sulfur. Ash fusion temperatures and properties of the CWFs were determined.

Sixty-day stability of all the CWFs was achievable through the use of a chemical stabilizer (Flocon). A correlation was found to describe stability as a function of the mass mean diameter, coal rank (expressed as volatile matter), and beneficiation. The Upper Elkhorn No. 3 CWF cleaned by froth flotation was a standout from the other three Upper Elkhorn CWFs. It required substantially less stabilizer. This may be due to the flotation reagents (methyl amyl alcohol and No. 2 diesel) used during the beneficiation process. Flocon degrades due to biological degradation, but it still maintains the CWF in suspension for two months. Flow characteristics of the CWFs were determined by using rotary and capillary viscometers in addition to measurements in tube flow. Most CWFs behaved similarly at low shear rates with similar rheograms. The flow characteristics of CWF in tubes was found to be independent of material.

Freeze-thaw tests of the CWF showed that they should not be allowed to freeze. This differed from results of past investigations. Some precautions in bulk storage and transportation would be needed to prevent the CWF from freezing. The use of freezing point depressants in the CWF could also be used to protect the fuel from exposure to decreased temperatures.

Atomization with three different atomizers showed that the Tecogen nozzle gave the best overall operation. The nozzle designed by Tecogen consisted of an annulus design with external mixing of fuel and air.

Several parameters dictate CWF characteristics, including coal loading. Studying the effect of loading in addition to other parameters (particle size distribution and coal type) can bring about a broader understanding of different CWF formulations. Another issue that arises is the different grind characteristics obtained from different types of mills. In addition, by blending differently ranked coals (i.e., subbituminous and bituminous) to produce CWF, a compliant fuel can be produced. However, the effect of blending different types of coal on CWF stability and rheology needs to be addressed. In order for large-scale CWF production to be practical, consistent CWF properties are required. The quality of the water (i.e., mineral content) may have an effect on the CWF properties. Therefore, the impact of water quality on CWF characteristics should be examined.

REFERENCES

1. Morgan, M.E. et al., "A Study of Yield Stress of CWF," Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization, New Orleans, LA, May 1985.
2. Cai, M. and Jiang, L., "Stability of Concentrated Coal Water Slurry," Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization, New Orleans, LA, May 1985.
3. Walters, A.B., "Chemical Effects of Beneficiation on Coal-Water Fuel Properties," Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization, New Orleans, LA, May 1985.
4. Turiani, R.M. et al., "Characterization, Stability, and Rheology of Coal-Water Mixtures," Eighth International Symposium on Coal Slurry Fuel Preparation and Utilization, Orlando, FL, May 1986.
5. Funk, J.E. et al., "Evaluation of CWM Dispersants Correlating Zeta Potential, pH, and Rheology," Eighth International Symposium on Coal Slurry Fuel Preparation and Utilization, Orlando, FL, May 1986.
6. Casassa, E.Z. and Toor, E.W., "Correlation Between Electrophoretic Mass Transport and Bulk Properties of Concentrated Coal Suspensions," Energy and Fuel, Vol. 2, No. 2, March-April 1988.
7. Berggren, M.H. and Bhasin, A.K., "Correlation of Coal-Water Slurry Fuel Solids Loadings with Coal Characteristics," Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization, New Orleans, LA, May 1985.
8. Smit, F.J. and Maas, D.J., "Preparation and Analysis of Low-Rank Coals for Combustion Applications," Final Report Contract Number DE-AC18-84FC10623, October 1986 (NTIS DE 87001034).
9. Berggren, M.H. and Swanson, W.W., "Additive Development for Ultra-Clean Coal Slurry Fuel," Final Report, DOE Contract No. DE-AC22-85PC80262, 1988.
10. Williams, J.A. et al., "Effect of Selected Additives on the Stability and Rheology of Coal-Water Mixtures," Seventh International Symposium on Coal Slurry Fuel Preparation and Utilization, New Orleans, LA, May 1985.
11. Miller, J.W. and Hoyt, H.L., "Evaluation of Polymers as Suspending Aids for Coal Water Slurries," Thirteenth International Conference on Coal and Slurry Technology, Denver, Colorado, April 1988.
12. Hoyt, H.L. and Moppett, F.K., "Use of Biocides in Polymer Stabilized Coal Water Slurries," Thirteenth International Conference on Coal and Slurry Technology, Denver, Colorado, April 1988.
13. Berggren, M.H. and Bhasin, A.K., "Correlation of Coal-Water Slurry Fuel Solids Loadings with Coal Characteristics," Presented at Seventh International Symposium on Coal-Slurry Fuels Preparation and Utilization, New Orleans, May 21-24, 1985.

14. Smit, F.J. and Maas, D.J., "Preparation and Analyses of Low-Rank Coals for Combustion Applications," Final Report Contract No. DE-AC18-84FC10623, October 1986 (NTIS DE 87001034).
15. Funk, James E., U.S. Patent Nos. 4,282,006, 4,441,887, and 4,477,259, August 4, 1981, April 10, 1984, and October 16, 1984, and related patents assigned to Alfred University Research Foundation.
16. Miller, B.G., "Coal-Water Slurry Fuel Utilization in Utility and Industrial Boilers," Chemical Engineering Progress, Volume 85, No. 3, March 1989, pp. 29-38.
17. Hammond, T.K. and Mathiesen, M.M., "Manufacture and Commercial Use of Carbogel Coal/Water Fuel in Canada," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 982-987.
18. Kuhner, S.W. and Malone, D.P., "Practical Aspects of Coal-Water Fuel Storage and Transportation; Pipeline, Truck, Rail," Proceedings of the Twelfth International Conference on Slurry Technology, March 31 - April 3, 1987, New Orleans, pp. 225-230.
19. Rossmetssl, N.P., Dussia, P.J., and Passman, R.A., "Quality Control Methods for the Production of ARC-COAL in a Commercial Plant," Proceedings, Seventh International Symposium on Coal-Slurry Fuels Preparation and Utilization, May 21-24, 1985, New Orleans, pp. 194-204.
20. Knell, E.W., Murphy, T.J., Flanigan, E.P., and Moxim, R.F., "The OXCE Fuel Company Coal-Water Mixture Demonstration Project," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 976-981.
21. Knell, E.W., Murphy, T.J., and Rakitsky, W.G., "OXCE Fuel Company CWF," Proceedings of the Tenth International Conference on Slurry Technology, Lake Tahoe, March 26-28, 1985, pp. 219-224.
22. Bhasin, A.K., Berggren, M.H., Ronzio, N.J., and Smit, F.J., "Chemical Coal Cleaning Process and Costs Refinement for Coal-Water Slurry Manufacture," Final Report Contract No. DE-AC21-83MC20700, December 31, 1985 (NTIS DE 86010793).
23. Berggren, M.H. and Swanson, W.W., "Additive Development for Ultra-Clean Coal-Slurry Fuel," Final Report Contract No. DE-AC22-85PC80262, May 24, 1988.
24. Berggren, M.H. and Swanson, W.W., "Development of Dispersing Additives for Ultra-Clean Coal-Slurry Fuels," Proceedings of the Twelfth International Conference on Slurry Technology, March 31 - April 3, 1987, New Orleans, pp. 265-270.
25. Purcell, R.J., Jr. and Sawyer, E.W., "Testing of Clay-Stabilized Coal-Water Slurries - Combustion and Loop Test Stability," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 423-436.

26. Shih, C.C., Motley, E.P., Meyers, R.A., Jones, J.F., Lim, W.Y., Anastasi, J.L., and Liberman, A., "Plant Equipment Selection and Performance Using Coal-Water Mixtures," Final Report Contract No. DE-AC22-82PC50270, July 1986 (NTIS DE 88004153).
27. Shih, C.C., Meyers, R.A., Motley, E.P., Jones, J.F., and Lim, W.Y., "Equipment Performance and Hydraulics Data from Phase II Testing of Coal-Water Mixtures," Proceedings, Eighth International Symposium on Coal Slurry Fuels Preparation and Utilization, Orlando, May 27-30, 1986, pp. 599-614.
28. Rossmelssl, N.P., Carlton, C.H., and Dussia, P.S., "Process Design, Cost, and Fuel Characterization for the Utilization of Coal-Water Fuels," Proceedings, Eighth International Symposium on Coal-Slurry Fuels Preparation and Utilization, Orlando, May 27-30, 1986, pp. 632-644.
29. Ishihara, T., Takahashi, K., Tanaka, E., and Nakabayashi, Y., "Pilot Plant Test of CWM Transportation at Wacotec in 1985," Proceedings, Eighth International Symposium on Coal-Slurry Fuels Preparation and Utilization, Orlando, May 27-30, 1986, pp. 864-877.
30. Nakabayashi, Y., Sato, N., Ito, H., Tatsumi, S., Kajibata, Y., and Takao, S., "Effect of Stabilizing Agents on the Rheology and the Stability of Coal-Water Mixture," Proceedings, Eighth International Symposium on Coal-Slurry Fuels Preparation and Utilization, Orlando, May 27-30, 1986, pp. 55-62.
31. Causilla, R. and Liu, E.H., "Design Considerations for Coal-Water Slurry Handling Systems at Utility and Industrial Plants," Proceedings, Seventh International Symposium on Coal-Slurry Fuels Preparation and Utilization, New Orleans, May 21-24, 1985, pp. 874-882.
32. Faulkner, A.R., "CWM Large Burner Development Tests and Demonstrations in the United States and Canada - 1983-1986," Proceedings, Eighth International Symposium on Coal-Slurry Fuels Preparation and Utilization, Orlando, May 27-30, 1986, pp. 717-727.
33. Electric Power Research Institute, "Coal-Water Slurry Test in an Industrial Boiler," EPRI Report Summary of Final Report CS-4268, October 15, 1985.
34. Causilla, H., Jr., Faulkner, A.R., Schmid, M.R., and O'Connor, H.W., "Barge Delivery of Coal-Water Slurry to Mystic Station Test Burn," Proceedings of the Tenth International Conference on Slurry Technology, Lake Tahoe, March 26-28, 1985, pp. 225-230.
35. Perkins, R.P., Manfred, R.K., and Taylor, B.E., "EPRI Industrial Coal-Water Slurry Demonstration," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 481-498.
36. Furman, R.C., "EPRI Coal-Water Slurry Demonstration Using Co-AL," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 548-556.
37. Wagner, J., Jr., Sommer, T.M., Taylor, B.E., and Johnson, S.A., "Coal-Water Mixture Firing in an Industrial Package Boiler - A User's Perspective," Proceedings, Seventh International Symposium on Coal-Slurry Fuels Preparation and Utilization, New Orleans, May 21-24, 1985, pp. 734-750.

38. Adelphi Center for Energy Studies, "Coal-Water-Slurry Pumping and Flow Tests," Report CS-3722, Electric Power Research Institute, October 1984.
39. Doohar, J.P., Cote, D., DiMeo, D., Malicki, N., and Wright, D., "Handling Properties of Coal-Water-Slurry Fuels," Proceedings, Seventh International Symposium on Coal-Slurry Fuels Preparation and Utilization, New Orleans, May 21-24, 1985, pp. 1057-1069.
40. Adelphi Center for Energy Studies, "Coal-Water-Slurry Loop Tests, Phase II," Final Report DOE/PC70269-T1, August 1986 (NTIS DE 86014427).
41. Doohar, J.P. et al., "Handling Properties of Coal/Water Slurries," Proceedings, Fifth International Symposium on Coal-Slurry Combustion and Technology, Tampa, April 25-27, 1983, Volume 2, pp. 1142-1156.
42. Batra, S.K., Kenney, R.B., and O'Toole, A., "Rheology and Pumping Characteristics of Coal-Water Slurry Fuels Prepared in a Columbia Chase Integrator," Proceedings, Fifth International Symposium on Coal-Slurry Combustion and Technology, Tampa, April 25-27, 1983, Volume 2, pp. 1119-1141.
43. Chen, J.L.S., Ekmann, J.M., and Ekmann, A.C., "Experimental Study of Coal-Slurry Flows in a Circular Duct," Proceedings of the Tenth International Conference on Slurry Technology, Lake Tahoe, Nevada, March 26-28, 1985, pp. 135-141.
44. Antonini, G., Francois, O., Gislais, P., Touret, A., and Girard, P., "A Direct Rheological Characterization of Highly Loaded Coal-Water Slurries Flowing Through Pipes," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 266-281.
45. Antonini, G., Francois, O., Gislais, P., Roux, R., and Girard, P., "Temperature Effects in the Handling Properties of Coal-Water Slurries," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 899-917.
46. Cook, D.A., Kearns, J.D., Smith, D.A., Rini, M.J., and LaFlesh, R.C., "C-E Canada CWM Nozzle Development and Firing Experience," Proceedings, Sixth International Symposium on Coal-Slurry Combustion and Technology, June 25-27, 1984, Orlando, Florida, pp. 993-1011.
47. Murphy, T.J., Flanigan, E.P., McCormick, R.J., and Goulet, A.B., "Laminar Flow Transport Properties of OXCE Fuel Company's Coal-Water Fuel," Proceedings of the Twelfth International Conference on Slurry Technology, New Orleans, March 31 - April 3, 1987, pp. 93-98.
48. Rosen, S.L., "Fundamental Principles of Polymeric Materials for Practicing Engineers," Barnes and Noble, New York, N.Y., 1971, pp. 180-187.
49. Balsavich, J.C., Becker, F.E., and Smolensky, L.A., "CWS-Fired Residential Warm-Air Heating System," Phase II Final Report, DE-AC22-87PC79650-13.

APPENDIX A
DATA ON PERIODIC REMIXING ON STABILITY

TABLE A.1

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type A: Upper Eikhorn HMS Coal, 13.0 μ m MMD, 0.34% A-23, 0.04% Flocon

Storage Time	Mixing Configuration	Cake Thickness, Inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-3/16	0	5/16	1/8
2 Weeks	0	4-13/16	3/16	1/4	3/8
3 Weeks	0	4-3/8	5/16	3/8	9/16
4 Weeks	0	4-1/16	1/2	3/8	11/16
1 Month	0	3-13/16	11/16	3/8	3/4
5 Weeks	0	3-7/8	7/16	5/16	1
6 Weeks	0	3-1/8	3/4	7/16	1-5/16
7 Weeks	0	2-5/8	13/16	9/16	1-5/8
8 Weeks	0	2-9/16	11/16	7/16	1-15/16
2 Months	0	2-11/16	3/8	9/16	2
Remix 5 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-1/2	0	0	1/8
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
2 Months	1	5-1/2	0	0	1/8
Remix 2 Times per Week					
1 Week	1	5-9/16	0	0	1/16
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-7/16	0	0	3/16
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-7/16	0	0	3/16
2 Months	1	5-3/8	0	0	1/4
Remix 1 Time per Week					
1 Week	1	5-9/16	0	0	1/16
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-1/2	0	0	1/8
4 Weeks	1	5-1/2	0	0	1/8
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-7/16	0	0	3/16
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-3/8	0	0	1/4
Remix Every 2 Weeks					
2 Weeks	4	5-5/8	0	0	0
4 Weeks	4	5-1/2	0	0	1/8
6 Weeks	4	5-1/2	0	0	1/8
8 Weeks	4	5-3/8	0	0	1/4

TABLE A.2

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type B: Upper Elkhorn HMS Coal, 9.0 μ m MMD, 0.42% A-23, No Flocon

Storage Time	Mixing Configuration	Cake Thickness, Inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-3/8	1/8	1/8	0
2 Weeks	0	4-5/8	1/2	3/8	1/8
3 Weeks	0	4-3/8	5/8	1/2	1/8
4 Weeks	0	3-1/2	1	1/2	5/8
1 Month	0	3-5/16	15/16	3/4	5/8
5 Weeks	0	3-1/16	13/16	11/16	1-1/16
6 Weeks	0	2-3/8	9/16	5/8	2-1/16
7 Weeks	0	2-1/8	0	15/16	2-9/16
8 Weeks	0	1-7/16	0	1-3/16	3
2 Months	0	1-1/8	0	1-3/16	3-5/16
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-9/16	0	0	1/16
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
2 Months	1	5-1/2	0	0	1/8
Remix 1 Time per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-9/16	0	0	1/16
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
Remix Every 2 Weeks					
2 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
Remix 1 Time per Month					
1 Month	5	5-1/2	0	0	1/8
2 Months	5	5-1/4	0	0	3/8

TABLE A.3

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type A: Upper Elkhorn HMS/Filtered Coal, 13.0 μ m MMD, 0.405% A-23, 0.04% Flocon

Storage Time	Mixing Configuration	Cake Thickness, Inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-1/4	1/8	3/16	1/16
2 Weeks	0	4-7/8	5/16	1/8	5/16
3 Weeks	0	4-9/16	1/4	3/8	7/16
4 Weeks	0	4-3/16	1/2	5/16	5/8
1 Month	0	4-3/16	7/16	5/16	11/16
5 Weeks	0	3-7/8	9/16	7/16	3/4
6 Weeks	0	3-9/16	9/16	3/8	1-1/8
7 Weeks	0	3-3/16	7/16	11/16	1-5/16
8 Weeks	0	2-7/8	5/8	7/16	1-11/16
2 Months	0	2-7/8	9/16	1/2	1-11/16
Remix 5 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-9/16	0	0	1/16
7 Weeks	1	5-9/16	0	0	1/16
8 Weeks	1	5-1/2	0	0	1/8
2 Months	1	5-1/2	0	0	1/8
Remix 2 Times per Week					
1 Week	1	5-9/16	0	0	1/16
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-8/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-9/16	0	0	1/16
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-3/8	0	0	1/4
2 Months	1	5-7/16	0	0	3/16
Remix 1 Time per Week					
1 Week	1	5-9/16	0	0	1/16
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-1/2	0	0	1/8
4 Weeks	1	5-1/2	0	0	1/8
5 Weeks	1	5-7/16	0	0	3/16
6 Weeks	1	5-1/2	0	0	1/8
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-7/16	0	0	3/16
Remix Every 2 Weeks					
2 Weeks	3	5-5/8	0	0	0
4 Weeks	3	5-1/2	0	0	1/8
6 Weeks	3	5-7/16	0	0	3/16
8 Weeks	3	5-3/8	0	0	1/4

TABLE A.4

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type B: Upper Elkhorn HMS/Filtered Coal, 13.0 μ m MMD, 0.47% A-23, 0.08% Flocon

Storage Time	Mixing Configuration	Cake Thickness, inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-3/8	3/16	0	1/16
2 Weeks	0	5-1/16	3/8	1/8	1/16
3 Weeks	0	4-15/16	7/16	1/8	<1/8
4 Weeks	0	4-15/16	3/8	1/8	3/16
1 Month	0	4-15/16	3/8	1/8	3/16
5 Weeks	0	4-3/4	7/16	3/16	1/4
6 Weeks	0	3-3/4	1-1/8	3/8	3/8
7 Weeks	0	4-7/16	7/16	5/16	7/16
8 Weeks	0	4-3/16	5/8	1/4	9/16
2 Months	0	3-15/16	9/16	9/16	9/16
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-1/2	0	0	<1/8
5 Weeks	1	5-1/2	0	0	<1/8
6 Weeks	1	5-7/16	0	0	3/16
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-7/16	0	0	3/16
2 Months	1	5-7/16	0	0	3/16
Remix 1 Time per Week					
1 Week	1	5-9/16	0	0	1/16
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-1/2	0	0	1/8
4 Weeks	1	5-1/2	0	0	1/8
5 Weeks	1	5-7/16	0	0	3/16
6 Weeks	1	5-7/16	0	0	3/16
7 Weeks	1	5-3/8	0	0	1/4
8 Weeks	1	5-3/8	0	0	1/4
Remix Every 2 Weeks					
2 Weeks	1	5-9/16	0	0	1/16
4 Weeks	2	5-7/16	0	0	3/16
6 Weeks	2	5-5/16	0	0	5/16
8 Weeks	2	5-1/16	0	0	9/16
Remix 1 Time per Month					
1 Month	2	5-3/16	0	0	7/16
2 Months	2	4-5/8	0	0	1

TABLE A.5

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type A: Upper Eikhorn Chemical Coal, 13.0 μ m MMD, 0.34% A-23, 0.02% Flocon

Storage Time	Mixing Configuration	Cake Thickness, inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	4-13/16	5/16	3/8	1/8
2 Weeks	0	4-1/4	3/8	7/16	9/16
3 Weeks	0	3-7/16	11/16	9/16	15/16
4 Weeks	0	2-3/4	1-5/16	3/4	1-3/16
1 Month	0	2-15/16	9/16	11/16	1-7/16
5 Weeks	0	2-3/8	3/4	13/16	1-11/16
6 Weeks	0	1-5/8	13/16	9/16	2-5/8
7 Weeks	0	1-5/8	0	13/16	3-3/16
8 Weeks	0	1-11/16	0	1/2	3-7/16
2 Months	0	1-5/8	0	1/4	3-3/4
Remix 5 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-1/2	0	0	1/8
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
2 Months	1	5-1/2	0	0	1/8
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-1/2	0	0	1/8
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-7/16	0	0	3/16
7 Weeks	1	5-7/16	0	0	3/16
8 Weeks	1	5-7/16	0	0	3/16
2 Months	1	5-7/16	0	0	3/16
Remix 1 Time per Week					
1 Week	2	5-5/8	0	0	0
2 Weeks	3	5-5/8	0	0	0
3 Weeks	3	5-9/16	0	0	1/16
4 Weeks	3	5-1/2	0	0	1/8
5 Weeks	3	5-7/16	0	0	3/16
6 Weeks	3	5-7/16	0	0	3/16
7 Weeks	3	5-1/2	0	0	1/8
8 Weeks	3	5-7/16	0	0	3/16
Remix Every 2 Weeks					
2 Weeks	5	5-5/8	0	0	0
4 Weeks	5	5-9/16	0	0	1/16
6 Weeks	5	5-3/8	0	0	1/4
8 Weeks	5	5-1/2	0	0	1/8

TABLE A.6

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type B: Upper Elkhorn Chemical Coal, 9.2 μ m MMD, 0.53% A-23, No Flocon

Storage Time	Mixing Configuration	Cake Thickness, Inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-7/16	0	1/8	1/16
2 Weeks	0	4-7/8	3/8	5/16	1/16
3 Weeks	0	4-7/16	5/8	5/16	1/4
4 Weeks	0	4-5/16	3/8	7/16	1/2
1 Month	0	4-3/16	1/2	3/8	9/16
5 Weeks	0	3-3/16	1/2	5/16	1
6 Weeks	0	3	13/16	9/16	1-1/4
7 Weeks	0	2-13/16	11/16	1/2	1-5/8
8 Weeks	0	2-5/8	3/4	1/2	1-3/4
2 Months	0	2-7/16	3/4	1/2	1-15/16
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
1 Month	1	5-9/16	0	0	1/16
5 Weeks	1	5-9/16	0	0	1/16
6 Weeks	1	5-1/2	0	0	1/8
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	1	5-1/2	0	0	1/8
2 Months	1	5-1/2	0	0	1/8
Remix 1 Time per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-9/16	0	0	1/16
3 Weeks	1	5-9/16	0	0	1/16
4 Weeks	1	5-9/16	0	0	1/16
5 Weeks	1	5-1/2	0	0	1/8
6 Weeks	1	5-1/2	0	0	1/8
7 Weeks	1	5-1/2	0	0	1/8
8 Weeks	2	5-7/16	0	0	3/16
Remix Every 2 Weeks					
2 Weeks	1	5-5/8	0	0	0
4 Weeks	2	5-9/16	0	0	1/16
6 Weeks	2	5-7/16	0	0	3/16
8 Weeks	3	5-3/8	0	0	1/4
Remix 1 Time per Month					
1 Month	3	5-7/16	0	0	3/16
2 Months	3	5-5/16	0	0	5/16

TABLE A.7

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type B: Illinois No. 6 HMS Coal, 13.0 μ m MMD, 0.72% A-23, No Flocon

Storage Time	Mixing Configuration	Cake Thickness, inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-9/16	1/16	0	0
2 Weeks	0	5-1/2	1/8	0	0
3 Weeks	0	5-3/16	7/16	0	0
4 Weeks	0	4-7/8	5/16	7/16	0
1 Month	0	4-11/16	1/4	11/16	0
5 Weeks	0	3-3/4	1	3/4	1/8
6 Weeks	0	1	3-5/16	1/2	13/16
7 Weeks	0	1-11/16	2-1/2	1/2	15/16
8 Weeks	0	2-7/8	1-1/4	1/2	1
2 Months	0	3	13/16	5/8	1-3/16
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	1/16	0
1 Month	1	5-9/16	0	1/16	0
5 Weeks	1	5-1/2	0	1/8	0
6 Weeks	1	5-1/2	0	1/8	0
7 Weeks	1	5-9/16	0	0	1/16
8 Weeks	1	5-7/16	0	3/16	0
2 Months	1	5-7/16	0	3/16	0
Remix 1 Time per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	1/16	0
5 Weeks	1	5-1/2	0	1/8	0
6 Weeks	1	5-1/2	0	1/8	0
7 Weeks	1	5-1/2	0	1/8	0
8 Weeks	1	5-1/2	0	0	1/8
Remix Every 2 Weeks					
2 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-9/16	0	1/16	0
3 Weeks	1	5-1/2	0	1/8	0
8 Weeks	1	5-7/16	0	1/8	1/16
Remix 1 Time per Month					
1 Month	1	5-5/8	0	0	0
2 Months	1	5-1/16	0	9/16	0

TABLE A.8

EFFECTS OF PERIODIC REMIXING ON STABILITY OF SLURRY FUEL
 Type B: Upper Elkhorn Flotation Coal, 13.0 μ m MMD, 0.466% A-23, No Flocon

Storage Time	Mixing Configuration	Cake Thickness, Inches			
		Soft Pack	Medium Pack	Hard Pack	Very Hard Pack
No Remixing					
1 Week	0	5-5/8	0	0	0
2 Weeks	0	5-3/8	1/4	0	0
3 Weeks	0	5-3/16	7/16	0	0
4 Weeks	0	3-7/8	1-3/4	0	0
1 Month	0	3-7/8	1-3/4	0	0
5 Weeks	0	1/2	5-1/8	0	0
6 Weeks	0	1/2	4-1/4	7/8	0
7 Weeks	0	1-1/4	2	2-3/8	0
8 Weeks	0	15/16	3	15/16	3/4
2 Months	0	7/8	2-1/8	1-3/16	1-7/16
Remix 2 Times per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-5/8	0	0	0
1 Month	1	5-1/2	1/8	0	0
5 Weeks	1	5-1/2	1/8	0	0
6 Weeks	1	5-7/16	3/16	0	0
7 Weeks	1	5	5/8	0	0
8 Weeks	1	5-7/16	0	3/16	0
2 Months	1	5-5/16	0	5/16	0
Remix 1 Time per Week					
1 Week	1	5-5/8	0	0	0
2 Weeks	1	5-5/8	0	0	0
3 Weeks	1	5-5/8	0	0	0
4 Weeks	1	5-5/8	0	0	0
5 Weeks	1	5-7/16	3/16	0	0
6 Weeks	1	5-3/8	1/4	0	0
7 Weeks	1	5-1/2	0	1/8	0
8 Weeks	1	5-7/16	3/16	0	0
Remix Every 2 Weeks					
2 Weeks	1	5-5/8	0	0	0
4 Weeks	5	5-1/8	1/2	0	0
6 Weeks	5	5-1/2	1/8	0	0
8 Weeks	5	5-5/8	0	0	0
Remix 1 Time per Month					
1 Month	5	5-5/8	0	0	0
2 Months	5	5-5/8	0	0	0

APPENDIX B

PLOTS OF HARD-PACK DEPTHS FOR VARIOUS REMIXING FREQUENCIES

Figure B.1 Type A Upper Elkhorn HMS Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.2 Type B Upper Elkhorn HMS Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.3 Type A Upper Elkhorn HMS/Filtration Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.4 Type B Upper Elkhorn HMS/Filtration Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.5 Type A Upper Elkhorn Chemical Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.6 Type B Upper Elkhorn Chemical Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.7 Type B Illinois No. 6 HMS Slurry Residual Hard Pack and Very Hard Pack Cake Depths

Figure B.8 Type B Upper Elkhorn Flotation Slurry Residual Hard Pack and Very Hard Pack Cake Depths

END

**DATE
FILMED**

4 / 08 / 92