DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Molecular and Polymeric Ceramic Precursors

Research Progress Report

December 1, 1990 - November 30, 1991

Larry G. Sneddon

The Trustees of the University of Pennsylvania
Philadelphia, Pennsylvania 19104

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, make any warranty, express or implied, or assumes any legal liability of responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

August, 1991

Prepared for

The U.S. DEPARTMENT OF ENERGY

AGREEMENT NO. DE-FG02-87ER13732

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TECHNICAL REPORT

Grant No. DE-FGO2-87ER13732

Project Title

"Molecular and Polymeric Ceramic Precursors"

Abstract

The development of new methods for the production of complex materials is one of the most important problems in modern solid state chemistry and materials science. This project is attempting to apply the synthetic principles which have evolved in inorganic and organometallic chemistry to the production of technologically important non-oxide ceramics, such as boron nitride, boron carbide and metal borides. Our recent work has now resulted in the production of new polymer systems, including poly(B-vinylborazine), polyvinylpentaborane and polyborazylene, that have proven to be high yield precursors to boron-based ceramic materials. Current work is now directed toward the synthesis of new types of molecular and polymeric boron-containing species and an exploration of the solid state properties of the ceramics that have been produced in these studies.

Summary of Scientific Progress

As an alternative to high-temperature powder techniques, there has recently been great interest in the development of polymer precursors to ceramic materials. Such routes would appear to offer a number of potential advantages: (1) a suitable polymer could have a precisely controlled stoichiometry with a composition which could be systematically varied to optimize ceramic properties, (2) the polymer could be formed into a desired shape or thin-film and then converted to the ceramic with possible retention of form, and (3) the polymer could undergo decomposition at low temperatures, enabling ceramic formation under milder conditions than those used in conventional techniques.

Our work has concentrated on the syntheses and chemical properties of new boron containing polymer systems that might serve as useful precursors to technologically important boron-based ceramics, including boron nitride, boron carbide and metal borides. Some of the most important results of our DOE sponsored research are briefly described in the following sections.

New Polymer Precursor Routes to Metal Borides.

Boron forms binary compounds with most metals and these materials are in general high-melting, extremely hard solids with high degrees of thermal stability and chemical inertness. In addition, many metal borides also have metallic like conductivity and/or unusual magnetic properties. As a result, these materials have numerous possible structural and electronic applications. Many of these applications will, however, require the development of new processable chemical or polymeric precursors in order to obtain these borides in film, coating, fiber or shaped material forms. We have recently reported the high yield syntheses of two metal borides, TiB_2 and ZrB_2 , by means of an potentially general synthetic approach that may prove to be useful for the production of a wide range of metal borides in processed forms.

The precursors are obtained by dispersing either TiO_2 or ZrO_2 in a decaborane/dinitrile polymer $(-B_{10}H_{12}N\equiv C-(CH_2)_5-C\equiv N-)_x$. When these precursor mixtures are heated to $>1450^\circ C$ the corresponding diborides are formed in high chemical yields ($>90\%$ based on metal) by a process that is proposed to involve the in situ generation of boron carbide and carbon followed by reaction to produce the boride.

Elemental analyses of the products show excellent purities, with only very low levels of carbon, hydrogen, oxygen and nitrogen. The XRD spectra of the powders indicate that they are highly crystalline and show no evidence for either unreacted MO_2 or for the formation of other ceramic materials, such as the metal nitrides, carbides or other complex oxides (ie MBO_3).

We have also found, depending upon the metal oxide particle size, polymer solution viscosity and the presence of a suitable surfactant, that a liquid MO_2 /polymer precursor dispersion may be obtained which can then be used for the generation of metal boride coatings. We have, for example, achieved

TiB₂ coatings on graphite. The poly(B-vinylborazine) is a solid. Such coatings are of potential importance for many technological applications including, for example, the protection of carbon from attack by molten metals in composite materials. We are now in the process of expanding our studies of the application of this polymer precursor technique to the production of a wider variety of both metal borides and other nonoxide metal ceramics (eg, silicides and nitrides), and to the generation of these materials in forms suitable for shaped and coated materials applications.

New Syntheses of Poly(B-Vinylborazine) and Poly(Styrene-co-B-Vinylborazine) Copolymers.

We previously reported that B-vinylborazine, the inorganic analogue of styrene, may be readily obtained via the RhH(CO)(PPh₃)₃ catalyzed reaction of borazine with acetylene and that poly(B-vinylborazine), the analogue of polystyrene, may then be produced by thermally induced polymerizations. In our original studies we found that insoluble polymeric materials result from thermal polymerizations of neat B-vinylborazine and only when polymerizations were carried out in the presence of added borazine could soluble polymers be obtained. We have now examined alternative methods and conditions for inducing vinylborazine polymerizations and have recently found that soluble polyvinylborazine homopolymers can be readily obtained by solution polymerization with the free radical initiator AIBN.

Thus, in contrast to the thermally induced polymerizations, when the polymerization of vinylborazine was carried out in benzene solution for 20 h in the presence of 1.6 mol% AIBN, a white polymeric solid was obtained that was completely soluble in solvents such as benzene or ethers. Molecular weight studies using size exclusion chromatography/low angle laser light scattering (LALLS) show $M_w = 18,000$ and $M_n = 10,700$ for the polymer prepared in this manner. The molecular weight distribution was skewed in the high molecular weight end, suggesting that some crosslinking or branching may have occurred, perhaps by the formation of B-N linkages such as found in the polyborazylene polymer discussed in the next section. The molecular weight of the polymer may also be controlled by varying the AIBN concentrations.

The discovery that soluble poly(vinylborazines) could be readily formed in solution at 80°C with the aid of AIBN initiator has opened the way to controlled copolymerization reactions and we have now been able to form a range of hybrid inorganic/organic poly(vinylborazine/styrene) copolymers.

As indicated in the following tables, polyborazylene compositions and molecular weights can be made in a reproducible manner by controlling the reactant ratios and initiator concentrations.

<u>% Styrene Feed</u>	<u>% Styrene Observed</u>	<u>Mw</u>
22	67	11,000
40	77	17,000
59	86	18,700
79	94	14,000
100	100	23,400

<u>mol% AIBN</u>	<u>Mw</u>
1.2	17,900
0.69	59,200
0.07	>500,000

We are now investigating the formation of other types of hybrid copolymers derived from the reactions of vinylborazine with, for example, acrylonitrile, butadiene, vinylsilanes and vinylphosphazenes. These copolymers may have many unusual properties, as well as serve as precursors to more complex ceramic materials with a range of solid state properties.

Synthesis and Ceramic Conversion Reactions of Polyborazylene.

Poly(B-vinylborazine) shows excellent conversions to boron nitride, but because of its carbon backbone, it requires pyrolysis under an ammonia atmosphere in order to achieve low-carbon boron nitride. In an effort to develop new boron nitride precursors that give improved ceramic yields and/or do not require the use of ammonia during the ceramic conversion step, we initiated investigations of the syntheses of alternative types of borazine based polymers.

Polyborazylene polymers composed of linked borazine rings analogous the organic poly(phenylene) polymers, were of particular interest because of their potentially high ceramic yields (95%) and their close structural relationship to boron nitride. Small dehydrodimers and oligomers of alkylated borazine have previously been prepared; however, only the N-B coupled dimer 1:2'-[B₃N₃H₅]₂ has been obtained from the parent B₃N₃H₆ system. Several studies of borazine have also reported the formation of white low volatile (perhaps polymeric) solids, but these materials were not identified. Thus, no tractable dehydrocoupled polymers derived from the parent borazine had previously been characterized.

Our initial investigations of the synthesis of poly(borazylene) focused on metal catalyzed synthetic routes; however, during the course of these studies we discovered that simply heating liquid borazine in vacuo at moderate temperatures results in a dehydrocoupling reaction to produce soluble polymeric materials in excellent yields.

The polymer is isolated as a white powder that is soluble in solvents such as THF and glyme, and that, according to size exclusion chromatography (SEC)/ low angle laser light scattering (LALLS) analysis has M_w 7,600 g/mol and M_n 3,400 g/mol. Elemental analyses of the polymer are consistent with the empirical formula of $B_3N_3H_3$, (linear poly(borazine) = $B_3N_3H_4$) suggesting the formation of a branched-chain or partially crosslinked structure. Evidence of chain branching was also found in the SEC/LALLS/UV studies. The detailed structure of the polymer has not yet been established; however, since small amounts of both the N:B coupled dimer ($1:2'-(B_3N_3H_5)_2$) and borazanaphthalene ($B_5N_5H_6$) were isolated in the volatile materials from the reaction, the polymer may have a complex structure, having linear, branched, and fused chain segments.

Because of its composition, high yield synthesis, and excellent solubilities, poly(borazylene) would appear to be an ideal chemical precursor to boron nitride. Indeed, bulk pyrolyses of the polymer under either argon or ammonia to 1200°C were found to result in the formation of white boron nitride powders in excellent purities and ceramic yields 85-93% (theoretical ceramic yield, 95%).

We are presently exploring the use of both poly(vinylborazine) and poly(borazylene) as precursors for the formation of boron nitride films, coatings and fibers. Because of its technological importance, one application that we have been particularly interested in is the use of polymeric precursors for the formation of boron nitride coatings on ceramic fibers in ceramic matrix composite materials. Boron nitride coated ceramic fibers have been shown to enhance the strength of a ceramic fiber/ceramic composite by decreasing the interfacial shear strength between the fiber and matrix and thus increase the potential for fiber pullout (toughness). We have achieved the formation of excellent quality boron nitride fiber coatings by simply dipping ceramic fiber bundles in glyme solutions of either poly(vinylborazine) or poly(borazylene) then heating the fiber under either an ammonia or argon atmosphere to $\sim 900^\circ\text{C}$. Scanning electron microscopy (SEM) and Auger electron spectroscopy (AES) studies of the resulting fibers have indicated that excellent BN coatings can be achieved on alumina, silicon carbide, silicon nitride or carbon fibers.

END

**DATE
FILMED**

01 / 22 / 92