SRI International

DOE/PC/89880--T4

DE92 007744

SRI Report No. 8209-6 - Quarterly Report No. 2 - 30 May 1990

HYDROTHERMAL PRETREATMENT OF COAL

David S. Ross, Director
Organic and Inorganic Chemistry Department

Covering the Period January 16 to April 15, 1990

Prepared for:

U. S. Department of Energy
Pittsburgh Energy Technology Center
P.O. Box 10940, MS 921-165
Pittsburgh, PA 15236

Contract No. DE-AC22-89PC89880

Approved:

David M. Golden
Laboratory Director
Chemistry Laboratory

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

We recently examined Argonne-supplied Wyodak coal under both thermal (no added water, under N₂) and hydrothermal (liquid water present, under N₂) conditions at 350°C for periods of 30 min and 5 hr. We found that the coal produces a tar that is deposited on the reactor insert walls solely at hydrothermal conditions. The shift from 30 min to 5 hr yields a tar that is more volatile and has a slightly increased molecular weight. The coals recovered from thermal and hydrothermal treatments are different by pyrolysis-field ionization mass spectrometry (py-FIMS). Specifically, the hydrothermal condition yields py-FIMS volatiles with a higher weight average molecular weight and greater volatility. They are thus less polar, a conclusion consistent with other py-FIMS data showing that the volatiles from the hydrothermally treated coal are lower in phenolics. Our results show that the phenols and catechols in the coal behave very differently. Our data are consistent with a scheme in which the catechol units in the coal engage in condensation at thermal conditions, probably through a catalyzed process related to acidic sites on the mineral matter. The phenols in contrast are unreactive. At hydrothermal conditions, on the other hand, both are released hydrolytically. Thus it appears that the presence of added water decreases or eliminates thermally promoted crosslinking tied to catechol condensation.

Unexpectedly, we see acetone and other simple ketones in the Wyodak pyrolysate from both the thermal and hydrothermal treatment. Acetone in some cases is the single most prominent product. These ketones are not seen, however, in the unconfined py-FIMS heating. The difference between confined and unconfined heating suggests that water evolved from the coal itself in confined heating acts in some hydrolytic fashion to liberate the ketones.

INTRODUCTION

We are examining the effects of hydrothermal treatment on the structure and reactivity of a series of coals. The studies are conducted in small bomb reactors with Pyrex inserts, under nitrogen, and with sufficient water added to ensure the presence of liquid water at conditions. Our work to the present has been with Argonne Premium samples of Wyodak (subbituminous) coal; the coal was "dried" before use by holding it overnight at 1 torr and 60°C. Initial studies at 150° and 250°C over 30 min showed that little change took place.

The present studies are at 350°C for periods of 30 min and 5 hr. Thermal treatment (no added water) runs are run as controls. The diagnostics included extensive pyrolysis field ionization mass spectrometry (py-FIMS) analysis. This procedure includes heating small, weighed samples of product at 2.5°C/min from ambient to 500°C and taking spectra of the volatiles at 20°-30° intervals.

RESULTS

Composition

Both thermal and hydrothermal treatments reduced the oxygen content of the coal by 30%, as shown in Table 1. At lower temperatures, the coal was unchanged. The O-loss is consistent with our earlier results with Illinois No. 6 coal, where almost 50% of the starting oxygen was lost (Ross et al., 1987), as well as with more recent accounts by Kahn et al. (1989), Solomon et al. (1988), and Olson et al. (1989).

Although the identical results for both the thermal and hydrothermal cases showed that added water played no direct role in the O-loss, the products resulting from the two treatments were very different. In the hydrothermal case, a tar representing 7%-8% of the starting coal was deposited on the Pyrex inserts, while for the thermal case, the inserts were clean except for small quantities of coal lightly sticking to the walls. This difference is shown in photographs of inserts in Figure 1. Thus, water appears to play an integral role in prompting the formation of the tar, some properties of which are discussed below.

(a) Thermal

(b) Hydrothermal

RP-8209-7

Figure 1. Reactor inserts from the treatment of Wyodak Coal at 350°C and 30 min.

Table 1
EFFECTS OF WATER ON WYODAK COAL
AT 350°C -- COMPOSITION

	Starting Coal	Treated Coal	
		Thermal	Hydrothermal
H/C	0.90, 0.92 0.91, 0.89	0.83	0.82
O/C ^a	0.27, 0.27 0.24, 0.24	0.17	0.16

^aOxygen determined by direct O analysis.

py-FIMS Volatiles and Tars

The differences in the coals recovered from the thermal and hydrothermal runs were demonstrated py-FIMS. For the thermal and hydrothermal cases, the py-FIMS volatiles represented 26% and 28% of the starting coal, respectively. Thus the tar deposited on the insert walls in the hydrothermal case is an additional product due solely to the added water. The weight average molecular weight and volatility profiles for the py-FIMS volatiles shown in Figure 2(a) and 2(b) are representative of data from several runs. The molecular weight profiles in 2(a) show increases with increasing temperature, with a downturn at around 400°C reflecting introduction of pyrolytic processes. The volatiles from the hydrothermally treated sample are heavier, while the profiles in Figure 2(b) show that those volatiles are also more volatile.

The py-FIMS volatiles from the hydrothermally treated coal must therefore be less polar, a point consistent with the py-FIMS difference spectrum shown in Figure 2(c). The spectrum shows a number of strong peaks below the zero-line for material up to m/z around 150. These peaks correspond almost entirely to phenols and dihydroxybenzenes (DHB); the latter were shown to be primarily catechols by analysis of the water recovered from the runs with the ratios phenol:catechol:[hydroquinone + resorcinol] = 3:6:1. Water thus brings about a deficit in oxygen-containing materials, and they are replaced by what we presume to be midrange hydrocarbon

CAM-320583-14

Figure 2. Py-FIMS-data from the volatiles evolved from samples of Wyodak coal thermally and hydrothermally treated at 350°C/30 min.
(a) weight average molecular weight; (b) percent volatile; (c) difference spectrum depicting the difference hydrothermal - thermal.

material. The peaks below the zero line include those for acetone and butanone;* their presence along with other simple ketones was confirmed in analysis of the recovered water. For some runs the acetone peak at m/z 58 was the strongest signal in the spectrum, a result discussed more fully below.

Additional data are shown in Table 2, including data on the phenols and catechols content of the py-FIMS volatiles, and data from recent 5-hr hydrothermal runs. The phenols and catechols

Table 2
EFFECTS OF WATER ON WYODAK COAL
AT 350°C -- pyFIMS VOLATILES^a

	Untreated	Thermal		Hydrothermal	
		30 min	5 hr	30 min	5 hr
Phenols ^b	16.8-19.9	17.2-19.5	23.0	10.9-11.9	12.6
Catechols ^b	17.8-18.7	10.8-13.3	8.6	10.2-11.8	13.3
$T_{1/2}(^{\circ}\text{C})^c$	395-400	377-395	425	340-350	410
$\bar{M}_w^d$	403-411	329-380	308	410-421	332

^aValues presented as ranges are inclusive for data from at least two runs.

^bPhenol and catechol values represent the sums of the responses for phenol and catechol and their C_1 , C_2 , and C_3 derivatives in the py-FIMS records. They reflect the contribution of each component in the total volatiles fraction, normalized to the value for the phenolic content of the 5 hr deposited tar in Table 3.

^cThe temperature at which one-half of the volatiles has passed into the instrument.

^dOverall weight average molecular weight.

levels are presented in terms of the contributions of the arenols and their respective C_1 , C_2 , and C_3 derivatives in the total volatiles fraction, and it is evident that they behave very differently. (The values are normalized to the 5 hr/catechol result in Table 3, below.) The phenols appear to be stable to thermal treatment, but their levels fall by about 40% following hydrothermal treatment. They are thus released from the coal matrix through hydrolysis and, as noted above, have been qualitatively identified in the recovered aqueous phase.

* Dr. Karl Vorres has informed us that acetone is not used in the preparation of the Argonne samples, and we used no acetone in our work. Thus the acetone and butanone were not present adventitiously.

Table 3
EFFECTS OF WATER ON WYODAK COAL
AT 350°C -- TARS^a

	30 min	5 hr
Phenols	3.2	1.3
Catechols	3.9	1.0
T _{1/2} (°C)	195	140
M _w	393	432

^aSee footnotes for Table 2. The tars were virtually fully volatile.

The catechols behave similarly for the hydrothermal case, but decidedly differently at thermal conditions. Their levels fall during thermal treatment by about 40% after 30 min and by a full factor of 2 after 5 hr. These strikingly lower values must be the result of thermally promoted condensations of catechol units within the coal matrix. They are thus involved in the generation of new crosslinks; they are increasingly tied into the structure and are therefore not released during the py-FIMS heating. This view is consistent with the recent account by Stein et al. (1989), who showed that dihydroxybenzenes, and catechols in particular, readily undergo condensation at these temperatures. (The work of Stein et al. is discussed further below). It is moreover in line with several observation describing the oxygen functionalities in lower rank coals as in large measure responsible for the retrogressive reactions (Suuberg et al., 1985; Derbyshire et al., 1986; Deshpande et al., 1988; Solomon et al., 1989) and suggests that the catechol units specifically could be responsible for much of the crosslinking. In the hydrothermal case, the similarly in results for both phenols and catechols shows that the hydrolytic role for water overrides the retrogressive chemistry, a result supported by the large relative quantities of catechols seen in the recovered aqueous phase.

Thus added water appears to reduce or perhaps fully eliminate the crosslinking process tied to catechols in lower rank coals. These results are summarized in a scheme depicting chemistry at 350°C. The subscript c refers to a unit within the coal matrix.

The $T_{1/2}$ and $\overline{M}_w$ values in Table 3 reflect the differences seen in Figure 2(a) and 2(b). Thus it appears that there are only small differences between the untreated and 30-min thermally treated coals. However, the presence of added water dramatically reduces $T_{1/2}$. The results of the 5-hr runs appear to be similar for both the thermal and hydrothermal conditions, but initial data show there to be considerable differences between the products. These findings will be discussed in our next report.

Table 3 contains data for the tars recovered from 30-min and 5-hr hydrothermal runs. For the latter, we were unable to obtain yield data due to inadvertent loss of material, and the work is being repeated. However, visual inspection showed the level of tar deposit to be only slightly greater than those from the 30-min runs, suggesting that most of the release takes place in the initial heating periods. However as the table shows, the tars are different. The extended treatment appears to lower the phenols and catechols content and decrease $T_{1/2}$, while not affecting the molecular weight substantially. The treatment thus appears to "upgrade" the tar, a curious result that is to be studied further.

DISCUSSION

These results must be related to the benefits noted by others following coal pretreatment with steam or liquid water (Deshpande et al., 1984; Brandes and Graf, 1987a,b; Bienkowski et al., 1987; Ross and Hirschon., 1990). They could as well be connected to the removal of Ca^{2+} and other mineral components by the water, similar to results reported by Tyler and Schafer, (1980), Mochida et al. (1989), and Deshpande et al. (1988).

However our results suggest that an additional factor is operating related to the chemistry described recently by Stein et al., (1989), as mentioned above. The account describes DHB pyrolysis at 250°-400°C, and it was found that the dihydroxybenzenes underwent *acid catalyzed*

condensations to polymeric products. Catechols were found to be more reactive than the other two isomers. We conclude therefore that

- Acid-catalyzed condensations of DHBs, catechols in particular, are responsible for much of the retrogressive chemistry in lower rank coals.
- The presence of water significantly lowers the high acidity otherwise present on clay surfaces so that the acid-catalyzed condensations are suppressed or eliminated.

Tannenbaum and Kaplan (1985) suggested similar "dilution" of acidity for results in geochemical studies related to hydrocarbon development in source rock.

Indeed, the generation of tars by added water has some resemblance to the generation of petroleum hydrocarbons in the hydrous pyrolysis of source rock, as reported in geochemical studies of the action of hydrothermal conditions in accelerating maturity in oil shale and other hydrocarbon-bearing materials (Lewan et al., 1981; Hoering, 1984; Comet et al., 1986). In those cases, the water and mineral phases act on "immature" regions of the kerogen to generate the hydrocarbons. These findings could in turn be related to the fact that, at hydrothermal conditions, water becomes an excellent solvent for hydrocarbons. Thus the mutual solubilities of water and long chain alkanes become very high in the 250°-350°C range (Skripka, 1979), and a large collection of arenes including naphthalene and tetralin are miscible in all proportions with water at 300°C (Schneider and Jockers, 1978). Although the connections between these different observations are not yet clear, we view the common hydrothermal thread running through them as significant.

We also observed acetone and other simple ketones in the pyrolysates of Wyodak coal. The significance of the observation is apparent in three ways. First, such compounds are not commonly reported in coal thermolysis studies, although Olson et al. (1989) observed cyclic ketones after aqueous treatment of Beulah lignite. Second, because these compounds are obviously oxygen-containing and mobile, they are significant to coal structure and to O functionality and, by extension, to crosslinking chemistry. Third, they are abundant particularly after the extended (5-hour) treatment. The py-FIMS study of the recovered, treated coal showed that acetone represented fully 8% of all the volatiles seen to 300°C, in contrast to the 3% and 4% for phenol and catechol, respectively. It is significant that all these prominent O-compounds are not merely deposited on the treated coal and available for instant evaporation into the spectrometer. Instead, after surviving a 5-hr/350°C treatment in liquid water, they emerge at high vacuum at around 150°C in the programmed heating. They thus appear to be strongly sorbed to clays and

perhaps other mineral surfaces in the coal, suggesting that the O-functionalities in the coal are not randomly distributed but are concentrated around the mineral inclusions in the organic phase. McKay and Blanche have found this condition to be the case for oil shale (1985).

Acetone and other simple ketones were observed only during confined treatment preceding py-FIMS analysis. They were clearly absent when untreated coal was heated in the evacuated inlet of the spectrometer. We suspect that this action is due to water from the coal accumulating in the samples even during the thermal (i.e., dry) treatment. Water thus plays an important, widely ranging, and not well understood role in the thermal chemistry of at least the lower rank coals.

REFERENCES

- Beinkowski, P. R., Narayan, R., Greenkorn, R. A., and Chao, K-C., *Ind. Eng. Chem. Res.*, **26**, 202-205 (1987).
- Brandes, S. D., and Graff, R. A., *Prepr. Fuel Div., Am. Chem. Soc.*, **32** (3), 385-393 (1987a).
- Brandes, S. D., and Graff, R. A., *Energy and Fuels*, **1**, 84-88 (1987b).
- Comet, P. A., McEvoy, J., Giger, W., and Douglas, A. G., *Org. Geochem.*, **9**, 171-182 (1986).
- Derbyshire, F., Davis, A., Epstein, M., and Stansberry, P., *Fuel*, **65**, 1233 (1986).
- Deshpande, G. V., Holder, G. D., Bishop, A. A., Gopal, J., and Wender, I., *Fuel*, **63**, 956-960 (1984).
- Deshpande, G. V., Solomon, P. R., and Serio, M. A., *Prepr. Fuel Div., Am. Chem. Soc.*, **33**, 310-321 (1988).
- Hoering, T. C., *Org. Geochem.* **5**, 267-278 (1984).
- Kahn, M. R., Chen, W-Y, and Suuberg, E., *Energy and Fuels*, **3**, 223-230 (1989).
- Lewan, M. D., Winters, J. C., and Williams, J. A., in *Advances in Organic Geochemistry 1979*, M. Bjorøy et al., Eds. (John Wiley and Sons, Ltd., Chichester, 1981), pp. 524-533.
- McKay, J. F., and Blanche, M. S., *Liquid Fuels Technology*, **3**, 489-521 (1985).
- Mochida, I., Sakata, R., and Sakanishi, K., *Fuel*, **68**, 306-310 (1989).
- Olson, E. S., Sharma, R. K., and Diehl, J. W., *Prepr. Fuel Div., Am. Chem. Soc.*, 832-838 (1989).
- Ross, D. S., Green, T. K., Mansani, R., and Hum, G., *Energy and Fuels*, **1**, 292-294 (1987).
- Ross, D. S., and Hirschon, A., *Prepr. Fuel Div., Am. Chem. Soc.*, **35**, 37-45 (1990).
- Schneider, G. M., and Jockers, M., *Ber. Bunsenges. Phys. Chem.* **82**, 576-582 (1978).
- Skripka, V. G., *Chemistry and Technology of Fuels and Oils*, **15**, 88-90 (1979).
- Solomon, P. R., Serio, M. A., Malhoua, R., and McMillen, D. F., *Advanced Fuel Research Quarterly Report for the Period Oct. 1 - Dec. 31, 1988*, DOE Contract No. DE-AC22-88PC88814 (1988).
- Solomon, P. R., Deshpande, G. V., Serio, M. A., Kroo, E., Schobert, H., and Burgess, C., *Prepr. Fuel Div., Am. Chem. Soc.*, **34**, 800-813 (1989).

Stein, S., Wang, F. M., and Senthilnathan, V. P., in *Proceedings of the 1989 International Conference on Coal Science*, (International Energy Agency, 1989), pp.165-168).

Suuberg, E. M., Lee, D., and Larsen, J., *Fuel* **64**, 1668 (1985).

Tannenbaum, E., and Kaplan, I. R., *Nature*, **317**, 708-709 (1985).

Tyler, R. J., and Schafer, H., *Fuel*, **59**, 487-498 (1980).

END

DATE
FILMED
3 12 7 1992

I