0000470

1 OF 1

TABLE 1

REDUCTION OF COBALT-BASED FISCHER-TROPSCH CATALYSTS

CATALYST	GAS	SPACE VELOCITY (V/V/h)	P (psig)	T. HISTORY (°C)	REFERENCE
----------	-----	---------------------------	-------------	--------------------	-----------

DOE/PC/79816--4

12/89

DOE/PC/79816--4

DE93 006470

Slurry Phase Fischer-Tropsch Synthesis:

Cobalt Plus a Water-Gas Shift Catalyst

Report for

January 1, 1989 to March 31, 1989

Report No.: DOE/PC79816-4

Contract No.: DE-AC22-87PC79816

by

Ian C. Yates,

Claire A. Chanenchuk,

and

Charles N. Satterfield

for

U.S. Department of Energy

Pittsburgh Energy Technology Center

P.O. Box 10940-MS 902-L

Pittsburgh, PA 15236

Attention: Dr. V.U.S. Rao, Project Manager

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Summary

Most of this quarter has been devoted to design, construction and installation of a new external catalyst reduction unit. In this report methods of reducing cobalt-based Fischer-Tropsch catalysts are reviewed, in an effort to develop an understanding of the important parameters which affect the reduction of cobalt catalysts. Design considerations for the external reduction unit are also presented.

Table of Contents

1. Introduction	1
2. Reduction of Cobalt-Based Fischer-Tropsch Catalysts.	2
2.1 Literature Review of Reduction Procedures.	2
2.2 Recommended Preparation and Reduction Procedures.	3
3. Design and Construction of Catalyst Reduction Unit.	4
3.1 Design Considerations for Catalyst Reduction Unit	5
3.2 Construction of Catalyst Reduction Unit	7
4. Future Work	9
5. References.	10
6. Tables.	11
7. Figures	12

1. Introduction

The stability, activity, and selectivity of a mechanical mixture of Cu/ZnO/Al₂O₃ and a reduced Co/MgO/SiO₂ have been presented in previous quarterly reports. The yield of C₅⁺ hydrocarbons of the combined catalyst system was comparable to the yield from potassium-promoted iron catalysts similar to those used at SASOL and oxygenates were much lower in concentration. However, the cobalt catalyst deactivated with time-on-stream.

To develop a more complete understanding of the activity and selectivity of cobalt-based Fischer-Tropsch catalysts, we must now study the cobalt catalysts on their own. In this report, we present a review of the methods of reducing cobalt-based Fischer-Tropsch which have been presented in the literature. Because the reduction cannot be performed in the Autoclave reactor, we have designed an external reduction unit. The temperature, pressure, and flow considerations which were incorporated into the design are presented here.

2. Reduction of Cobalt-Based Fischer-Tropsch Catalysts

In order to develop a reduction procedure that will provide repeatable activity and selectivity for the cobalt catalyst that we have, a review of the available literature on cobalt catalysts has been performed. This includes reduction procedures used in large plants as well as in research facilities.

2.1 Literature Review of Reduction Procedures

Table 1 summarizes the reduction procedures that are in the literature. Particular attention is given to the composition of the reducing gas and to the temperature profile used during reduction. Generally, the catalysts are reduced in hydrogen and temperature is increased from ambient to between 350°C and 400°C over 4 to 6 h. The catalyst is then held at this maximum temperature for between 2 and 16 h.

The most useful information on the effects of different reduction procedures is provided in literature published in the 1950s. Cobalt-based catalysts were developed and used in Germany from 1936 to 1945 (Anderson, 1984). Therefore, a large fraction of the literature which describes the reduction of cobalt Fischer-Tropsch catalysts comes from data collected in Germany by Ruhrchemie. These data are summarized and analyzed by Storch, et al. (1951) and Storch, et al. (1959). Table 1 shows that most of the recent procedures for the reduction of cobalt catalysts are similar to those outlined by Storch and co-workers. Deviations from the "standard" reduction procedures

are generally not explained. As a result, very little can be gained from examining recent work.

On the basis of their own work at the Bureau of Mines and review of work done in Germany, Storch, et al. (1951, 1959) make four important conclusions about the reduction of $\text{Co/ThO}_2/\text{kieselguhr}$ and $\text{Co/ThO}_2/\text{MgO/kieselguhr}$ catalysts.

1. Sintering must be avoided during reduction. Hence, reduction should be performed in a short bed, with a high space velocity of hydrogen, at the lowest temperature possible, and in the shortest time possible.

2. The most active catalysts were obtained by ending the reduction before all the cobalt was reduced to metal. The most active catalysts had between 55 and 70 percent of available Co reduced. Unreduced CoO was speculated to prevent sintering of the catalyst.

3. When cobalt-based catalysts were reduced and then subsequently carbided with carbon monoxide, the activity of the catalyst was markedly less. A completely carbided sample, presumed to have 100 percent of the cobalt as Co_2C , was shown to be inactive for the Fischer-Tropsch synthesis.

4. When MgO was present the catalyst was harder to reduce, and thus a maximum reduction temperature of 400°C is recommended for $\text{Co/ThO}_2/\text{MgO/kieselguhr}$ as compared to 360°C for $\text{Co/ThO}_2/\text{kieselguhr}$.

2.2 Recommended Preparation and Reduction Procedure

1. The catalyst is ground to the desired particle size (50 to 90 μm) and calcined overnight at 100°C in an oven to remove any water from the catalyst sample. This is particularly important as the unreduced catalyst is reported to have a high moisture content.

2. The catalyst is reduced in 3000 V/V/h pre-purified hydrogen at atmospheric pressure. For the purpose of the space velocity calculations, a catalyst density of 0.65 g/cm^3 will be used.

3. On the basis of the above literature, the following temperature profile is recommended:

A. 100°C for $\frac{1}{2}$ to 1 hour.

B. 200°C for $\frac{1}{2}$ to 1 hour.

C. 300°C for $\frac{1}{2}$ to 1 hour.

D. Heating in 10°C increments from 300°C to 365°C . The temperature should be allowed to level off at each increment for at least $\frac{1}{4}$ hour.

E. 365°C for 16 hours.

3. Design and Construction of Catalyst Reduction Unit

To reliably and repeatably reduce a cobalt-based Fischer-Tropsch catalyst at high temperatures, an external reduction unit must be used. Following reduction, the catalyst must be transferred from this external reduction unit

to the reactor. The reduction unit should have excellent temperature, pressure, and flow control to ensure proper reduction of the catalyst.

The following sections describe the design considerations and construction of the equipment that has been performed.

3.1 Design Considerations for Catalyst Reduction Unit

The high temperature and high gas flow rates required for reduction of cobalt catalysts cause excessive carry-over of the octacosane slurry when reduction is performed in the 1-liter Autoclave reactor. Therefore, an external reduction unit must be used and the reduced catalyst must then be transferred from this external unit to the reactor under an inert atmosphere. The reduction system should prevent entrainment of the catalyst during reduction and have the flexibility to allow addition of the catalyst to the Autoclave reactor. The reduction unit must also have superior temperature, pressure, and flow control to insure reliable and repeatable reduction of the catalysts.

Fitting the reduction tube with two sintered frits, one of which is removable, gives the unit the capability to prevent catalyst entrainment during reduction and allows transfer of the catalyst to the Autoclave reactor. The catalyst particles are ground to 50 to 90 μm prior to reduction, thus 7 μm frits are used to hold the catalyst within the fluidized bed during reduction. These frits are placed above and below the catalyst. The frit above the catalyst is removable allowing subsequent removal of the reduced catalyst from

the tube. The reduction tube is fitted with a transfer tube which facilitates the catalyst transfer through the side-port of the 1-liter Autoclave reactor.

Reduction must be performed under isothermal conditions to ensure complete and uniform reduction of all catalyst. Further, good temperature control is required for the "ramping" of the temperature at the beginning of the reduction procedure. The required temperature control can be best achieved with a tube-furnace. Tube furnaces offer several significant advantages over a sand-baths. Sand baths require excessively long times to heat up and cool down. Conversely, tube furnaces have extremely fast response times. In addition, tube furnaces are less expensive and cleaner and simpler to operate than sand baths.

The outlet and inlet lines of the reduction tube must be heated and controlled. A preheated feed is required due to the high throughputs of the reduction gas. Heating tape on the feed lines and a packed preheating zone within the reduction tube ensure that gas entering the reaction zone is at the reduction temperature. In addition, because high water concentrations within the reduction tube adversely affect the extent of reduction, the outlet line must be heated with heating tape to prevent condensation of water, a reaction by-product. The temperature of these heating tapes will be controlled with Varian variacs and monitored with J-type thermocouples.

Ideally, reduction would be performed at atmospheric pressure. However, as a result of the filters within the reduction tube, a pressure drop exists across the reactor. Thus, because atmospheric pressure is unattainable, a

controlled consistent pressure is desired. This is important because the rate of reduction is directly related to the partial pressure of hydrogen. The pressure of the reduction tube will be controlled with a back-pressure regulator downstream of the reduction tube.

The flow to the reduction tube will be controlled with upstream mass flow controllers. The existing mass flow controllers on the Autoclave reactor manifolds will be used to provide constant flow rates. The high flow rates of the reducing gas could cause considerable channeling through the reaction zone. To prevent this feed bypassing, the bottom half of the reduction tube will be packed with inert beads. As discussed earlier, these beads also preheat the reducing gas.

3.2 Construction of Catalyst Reduction Unit

Figure 1 is a schematic of this reduction system. The unit will consist of a feed section, a reduction tube, or reactor, and a tube furnace with an accompanying controller. Figure 2 shows an expanded schematic of the reduction tube. The temperature of the reduction tube will be held constant using a Model 55122-1 Lindberg single-zone tube furnace and a Model 55114-P Lindberg programmable single-zone control console. This thermally-efficient furnace system will allow the required three-stage ramping of the reduction temperature up to 300°C.

The reducing gas, fed through Brooks Model 5850-E mass-flow controllers, will enter the bottom of the isothermal reduction tube. The lower section of this tube will be packed with inert 5 mm diameter glass beads which will pre-

heat the gases and provide an even distribution of the flow. The upper section of the reactor will be packed with 25 to 75 g of crushed and sieved catalyst. Catalyst reduction will occur in this upper reaction zone where a special design has been incorporated to guarantee that product gases, such as water, are swept away quickly. This will eliminate the possibility of re-oxidation and ensure that the reduction goes to completion. The product gases are vented through bubble flow meters which can be used to verify flow rates.

Upon complete reduction, the catalyst will be cooled to room temperature. The upper frit of the reduction tube will be removed while the catalyst is under a steady but low flow of helium gas to prevent re-oxidation of the catalyst. The reactor will then be closed, pressurized with helium, removed from the apparatus, and weighed. Comparing the weight before and after reduction will allow determination of the extent of reduction of the catalyst. The reduction tube will be fitted with a transfer line and connected to the side-port of the 1-liter Autoclave reactor. At this point, the 1-liter Autoclave, which will contain molten recrystallized octacosane, will be under helium. The catalyst will be blown out of the reduction tube with helium.

4. Future Work

1. The construction and leak-testing of the reduction unit should be completed soon. This construction will include the installation of a new fume hood which is being performed by outside contractors.

2. Following the shake-down of the equipment, the cobalt catalyst will be reduced and experiments to study the activity and selectivity will be performed.

References

- Anderson, R.B., The Fischer-Tropsch Synthesis, Academic Press Inc., Orlando, 1984.
- Beuther, H., Kibby, C.L., Kobylinski, T.P., and Pannell, R.B., United States Patent 4,399,234, August 16, 1983.
- Dent, A.L., and Lin, M., Adv. Chem. Ser., 178, 47 (1979).
- Lu, D.C., A Kinetic Study of the Modified Fischer-Tropsch Synthesis over an Alumina-Supported Cobalt Oxide Catalyst, Ph.D. Thesis, Arizona State University, 1985.
- Newsome, D.S., Catal. Rev-Sci. Eng., 21(2), 275 (1980).
- Reuel, R.C. and Bartholemew, C.H., J. Catal., 85, 78 (1984).
- Storch, H.H., Anderson, R.B., Hofer, J., Hawk, C., Anderson, H., and Golumbic, N., Synthetic Liquid Fuels from Hydrogenation of Carbon Monoxide, United States Bureau of Mines, Technical Paper No. 709 (1948) and Bulletin 578 (1959).
- Storch, H.H., Golumbic, N., and Anderson, R.B., The Fischer-Tropsch and Related Syntheses, Wiley, New York, 1951.
- Wang, J., Physical, Chemical, and Catalytic Properties of Borided Cobalt Fischer Tropsch Catalysts, Ph.D. Thesis, Brigham Young University, 1987.
- Yang, C-H., Massoth, F.E., and Oblad, A.G., Adv. Chem. Ser., 178, 35 (1979).
- Yates, I.C., Satterfield, C.N., Slurry Phase Fischer-Tropsch Synthesis: Cobalt plus a Water-Gas-Shift Catalyst, Quarterly Report from Inception to June 30, 1988, 1988a.
- Yates, I.C., Satterfield, C.N., Slurry Phase Fischer-Tropsch Synthesis: Cobalt plus a Water-Gas-Shift Catalyst, Quarterly Report from July 1 to September 31, 1988b.
- Yates, I.C., Satterfield, C.N., Slurry Phase Fischer-Tropsch Synthesis: Cobalt plus a Water-Gas-Shift Catalyst, Quarterly Report from October 1 to December 31, 1988, 1988c.
- Zhang, X., Fischer-Tropsch Synthesis over Cobalt Catalysts: A Study with Isotopic Methods, Ph.D. Thesis, University of Pittsburgh, 1986.

TABLE 1

REDUCTION OF COBALT-BASED FISCHER-TROPSCH CATALYSTS

CATALYST	GAS	SPACE VELOCITY (V/V/h)	P (psig)	T. HISTORY (°C)	REFERENCE
Co/ThO ₂ /MgO/ kieselguhr (used by Ruhrchemie in plant)	75 H ₂ / N ₂	10000	Not Given	1 h at 400°C	Storch, et al., 1951.
Co/ThO ₂ /MgO/ kieselguhr	H ₂	No flow 3000	0	2 h to 400°C 2 h at 400°C	Storch, et al., 1951.
Co/ThO ₂ / kieselguhr	H ₂	250 to 3000	0	1 h at 250°C 2 h at 250°C 2 h at 300°C 2 h at 330°C 5 h at 360°C	Storch, et al., 1951.
Co/ThO ₂ /MgO/ kieselguhr	H ₂	250 to 3000	0	1 h at 250°C 2 h at 250°C 2 h at 300°C 2 h at 330°C 5 h at 400°C	Storch, et al., 1951.
Co/Cu/Al ₂ O ₃	H ₂	Not given	5	2 h at 250°C 4 h at 510°C	Yang, et al., 1979.
Co/M/Al ₂ O ₃ Co/M/kies. M=Cr,Cu,Mn w/K	H ₂	900	35	16 h at 400°C	Dent and Lin, 1979.
Co/Fe	H ₂	4000	0	1 h at 300°C 2 h at 450°C	Nakamura, et al. 1979.
	10 vol% CO in helium		—	16 h at 350°C	
Co/Ru/ThO ₂ / Al ₂ O ₃	5% H ₂ /N ₂ H ₂	1000	Not Given	1 h at 100°C 2 h at 200°C 16 h at 360°C 16 h at 200°C	Seuther, et al., 1953.
	2% Air/N ₂				
Co/Al ₂ O ₃ Co/ThO ₂	H ₂	Not given	0	16 h at 400°C 1 h at 300°C	Reuel and Bartholemew, 1984.
Co/Al ₂ O ₃	H ₂	1000	140	4 h at 400°C	Lu, 1985.
Co/SiO ₂	H ₂	Not given	0	12 h at 350°C	Zhang, 1986.
Co Co/B	H ₂	Not given	0	16 h at 400°C	Wang, 1987.

Figure 1: Catalyst Reduction System: A Pressure Regulator; B Filter Drier; C Mass-Flow Controller; D Back-Pressure Regulator; E Two-Way Valve; F Pressure-Relief Valve; G Needle Valve; H Pressure Gauge; I Tube Furnace; J Packed Preheating Zone; K 7 μm Filter; L Thermocouple; M Removable 7 μm Filter; N 3-Way Valve; O Soap-film Flowmeter

NOT TO SCALE

INSTALLATION SPECIFICATIONS	
17.5" LONG. FIT TIGHTLY AROUND 3/4" O.D. INNER TUBE.	
18.75" LONG. CENTERED INSIDE 1" O.D. OUTER TUBE.	
1/8" SIDE SCREWED AND WELDED TO 3/4" INNER TUBE.	
3/8" HOLE DRILLED IN 1" O.D. OUTER TUBE.	
WELD TO INSIDE OF 3/4" O.D. INNER TUBE.	
WELDED TO PART #4.	
UNSCREWED AND REMOVE FROM RIGHT SIDE OF 3/4" O.D. TUBE.	
WELD TO INSIDE OF 3/4" O.D. INNER TUBE.	
LEAK-TIGHT FITTINGS TO APPROX. 500 PSIG.	
LEAK-TIGHT FITTINGS TO APPROX. 500 PSIG.	

PART	DESCRIPTION
A	1" O.D. 316 SS TUBE (S.W.G. GAGE 12, 0.11" WALL)
B	3/4" O.D. 316 SS TUBE (S.W.G. GAGE 12, 0.11" WALL)
1	1/8" TO 1/16" 316 SS SWAGelok REDUCER
2	316 SS FILTER, 7 MICRON SINTERED
3	1/2" DIAM. 316 SS FILTER, 7 MICRON SINTERED
4	316 SS THREADED FITTING WITH HEX SOCKET FOR SCREWING (RETAINING WALL LARGER THAN INSIDE DIAM. OF PART #4A)
4A	316 SS THREADED MOUNT FOR PART 4
5	316 SS 3/4" SWAGelok NUT, FRONT AND BACK FEMALE
6	3/4" TO 1/2" 316 SS SWAGelok REDUCER

Figure 2: Reduction Tube

END

DATE
FILMED
3/19/93