NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

I
DOE/ER/45132--T1

DE92 009024

DYNAMICS AND PATTERN SELECTION AT THE CRYSTAL-MELT INTERFACE

PROGRESS REPORT #4

For the Period March 1, 1989 - February 28, 1990

Prepared for

THE U. S. DEPARTMENT OF ENERGY
DE-FG02-84ER45132

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Prepared by:
Professor H. Z. Cummins
Principal Investigator
Department of Physics
The City College of CUNY
Convent Avenue @ 138th Street
New York, NY 10031

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

II. SUMMARY OF RESULTS OF PRIOR D.O.E. GRANTS

A. LIGHT SCATTERING AT THE CRYSTAL-MELT INTERFACE

Our investigations of dynamic light scattering from the crystal-melt interface in salol first established that oscillatory scattering occurs at the crystal surface and is caused by growing ledges of screw dislocations, while relaxational scattering occurs in the fluid boundary layer.^(a,b) We proposed an explanation for the relaxational scattering based on the nucleation of gaseous microbubbles during solidification^(c) and subsequently found that similar scattering occurs in the plastic crystal cyclohexanol.^(d)

Recently we have obtained direct visual verification of the existence of microbubbles and have shown that in slow prolonged growth of large crystals the bubbles can become sufficiently large to be trapped by the advancing surface of the crystal. These results are being prepared for publication, and a preliminary report is included in Section V of this proposal.

B. MORPHOLOGICAL INSTABILITY AND PATTERN SELECTION

We completed and published a study of the Mullins-Sekerka instability in succinonitrile in which videomicroscopy and computer image analysis techniques were used to determine the linear growth coefficient of each spatial Fourier component of the interface.^(e) Because these Fourier spectra were found to be extremely noisy, we undertook a study of the role of noise in the initial stage of the instability.^(f) We have also conducted preliminary studies of the coarsening stage and of steady-state pattern selection in this system. Using a new directional solidification apparatus, we have made preliminary studies of the cellular instability during directional solidification of succinonitrile-acetone mixtures and have begun an investigation of the response of dendrites in this material to sudden changes in growth velocity.

C. SIDEBRANCHING

A microscope light scattering spectrometer has been constructed and tested and is being used to probe shape fluctuations near the dendritic tip associated with sidebranching. This apparatus has also been configured to study the effects of localized periodic perturbations near the dendrite tip which should theoretically induce synchronization of the sidebranching process.

PUBLICATIONS - (References for Section II)

a. **Asymmetry of Dynamics at the Growing Crystal-Melt Interface**, O.N. Mesquita, D.G. Neal, M. Copie and H.Z. Cummins, Phys. Rev. B 29, 1345 (1984).

b. **Dynamics at the Nonequilibrium Crystal-Melt Interface**, O.N. Mesquita and H.Z. Cummins, Physico-Chemical Hydrodynamics 5, 389 (1984).

c. **Origin of the Diffusional Light Scattering at the Non-Equilibrium Crystal-Melt Interface**, H.Z. Cummins, G. Livescu, Henry Chou and M.R. Srinivasan, Solid State Commun. 60, 857 (1986). [Appendix I]

d. **Dynamic Light Scattering at the Nonequilibrium Crystal-Melt Interface in Cyclohexanol**, G. Livescu, M.R. Srinivasan, Henry Chou and H.Z. Cummins, Phys. Rev. A 36, 2293 (1987). [Appendix II]

e. **Evolution of the Dendritic Instability in Solidifying Succinonitrile**, Henry Chou and H.Z. Cummins, Phys. Rev. Lett. 61, 173 (1988). [Appendix III]

f. **Role of Noise in the Initial Stage of Solidification Instability**, K.W. Qian, Henry Chou, M. Muschol and H.Z. Cummins, Phys. Rev. B 39, 2529 (1989). [Appendix IV]

B. CURRENT RESEARCH

1. Free Growth into the Undercooled Melt

During the current grant period we completed a computerized videomicroscopy study of the early stages of the two-dimensional dendritic instability in succinonitrile starting from a flat interface.⁶ The results of this experiment are included as Appendix III. We found that the interface is initially roughly sinusoidal as shown in Fig. 2 of Appendix III, and that the Fourier amplitudes ϵ_k in the unstable k -range grow approximately exponentially with time as predicted by Eq. (3.5). However, the design of our experiment caused the melt temperature to change during solidification so that it was not possible to test the Mullins-Sekerka theory quantitatively, although its predictions were qualitatively confirmed, as shown in Fig. 1 of Appendix III. (We believe that the same problem also occurred in the Coriell ice cylinder experiments.⁴) The origin of this problem is that in order to initially stabilize the flat interface it is necessary to impose a positive temperature gradient on the sample. When the melt is then cooled, the interface begins to move immediately so that the uniformly undercooled melt assumed to exist in theoretical analyses cannot be achieved.

We have therefore constructed a new experimental setup in which the sample will be completely melted and uniformly undercooled. Crystal growth will be initiated by quickly chilling a platinum wire which is embedded in the sample cell, nucleating a seed. This will create an initially round (or nearly round) crystal.

In contrast to the planar geometry with its broadband instability of the crystallizing interface, the Mullins-Sekerka instability of a spherical or cylindrical crystal growing into its undercooled melt occurs in a discrete set of modes. Furthermore, each of these modes is stable until the droplet grows beyond a certain mode-specific threshold. This threshold can be expressed in multiples of the critical radius of nucleation:¹

$$\frac{R^*_j}{R^*} = 1 + \frac{1}{2}(j+2)(2j+1) \quad (3.13)$$

where $R^*(j)$ is the critical radius for the j 'th spherical harmonic mode to go unstable, and $R^* = 2d_0/\Delta$ is the critical radius of nucleation.

Figure 1 shows a schematic overview of the new experimental apparatus. The sample is positioned inside the double thermostated sample holder on top of the Nikon microscope stage. The separate photo- and video ports on the microscope allow the recording of the growth process on either 35mm film or videotape. The videotapes are then processed by a Data Translation quick-capture image processing board inside the Mac-II computer. An additional monitor allows us to check the images while they are recorded by the VCR.

The new sample cell consists of two flat glass plates, 1.6mm thick and 50.8mm in diameter. They are fused together around their circumference leaving a 50µm spacing between them. Two glass stems are connected to one of the two glass plates (see Figure 2). To fill the cell with the crystallizing material, the two stems can be connected to a vacuum distillation apparatus. After the multiply distilled material fills the space between the glass plates, the two stems are then sealed off; this assures that the crystallizing material is protected against any contamination. As shown in the figure, a fine platinum wire is embedded in the sample for initiation of crystallization. This will enable us to study a variety of different materials in solidification experiments, most of which have to be highly purified before use.

Figure 2 shows a cross section of the double sample thermostat placed in the opening of the microscope stage. The thermostat has two shells. An outer aluminum shell provides a stable (within .1K) heat sink about three degrees below the operating point of the inner shell. The inner copper shell controls the temperature of the sample against continuous heat loss to the outer shell. This way we are presently able to reach temperature stability down to the millikelvin range. Both shells are heated by flat annular heating element (Minco) which are fixed to the metal surfaces with thermally-conductive epoxy. Both shells have small holes for thermistors which provide feedback to the YSI-72 temperature controllers used to regulate the temperature. In order to observe the growth process there is an opening through the center of the thermostat, 20mm in diameter, covered with a total of seven sapphire windows, each 1mm thick. The heat loss through the windows is minimal, and we still have enough access for observation of the experiment. The two shells sit on a plastic ring which thermally insulates the thermostat from the microscope

Figure 1. Schematic overview of apparatus for computerized videomicroscopy of solidification instability and free dendritic growth.

Figure 2. Top: Cross-section of double thermostatted cell holder for solidification experiments with cylindrical geometry. Bottom: Cross-section and top view of cylindrical glass sample cell with platinum wire for nucleation of a crystal in the undercooled melt.

stage and vice versa.

We are using a Nikon Diaphot microscope for our observations. It is an inverted microscope which gives us more space to build up our sample holders on top of the stage. Since our sample cell sits inside the thermostat, we need objectives with a long working distance in order to get our cells into focus. Currently we are using a 4x and 10x long working distance objective. Together with the 10x eyepiece this yields a magnification of 40x and 100x respectively. The field of view with the 10x objective is about 200 μ m square.

The microscope has two ports for connecting a 35mm photo camera and a video camera. The video port can be used with a 1x, 2.5x or 5x projection lens. The photo camera used is a Nikon N2000 with a multidata back for labelling prints. Our video camera is a Dage-MTI video camera with a NuVicon tube.

The images from the video camera are recorded by a Magnavox digital VCR model VR9645AT01 with still frame and single frame advance feature. Its video output is connected to a Data Translation Quickcapture image analysis board inside a Macintosh-II computer. The image analysis board digitizes the incoming pictures and displays them on the computer screen. They can be manipulated with an image calculator, built-in high- and low-frequency filters and edge detectors. Beyond that, the computer enables us to write our custom-made software for our special image processing needs, especially the precise and reliable location of our moving crystallization front. The programs for the extraction of our interface positions are currently being developed.

The Mac-II is also interfaced to the mainframe Science Division VAX in our department which gives us access to a broad variety of subroutines and mathematical libraries.

2. Anisotropic Surface Tension

Anisotropy plays a central role in the solvability theory of dendritic crystal growth. Without anisotropy there is no steady state solution to equation 3.11 that includes surface tension. Anisotropy determines the selected velocity of the dendritic tip as well. In order to test the theory it is therefore essential to have a reliable knowledge of its value. Since it is a difficult quantity to measure, there have been very few serious attempts to measure it carefully.^{22,23}

The only published data on the anisotropy of succinonitrile is that of M. Glicksman for the equilibrium shape of liquid droplets inside a bulk solid matrix.³² Our experience has shown that liquid droplets seem to interact with each other over large distances which tends to deform their equilibrium shape. We therefore want to repeat the measurements of the succinonitrile equilibrium shape in our system but with single crystallite growing or shrinking very slowly or a single liquid droplet inside a uniform single crystal. Here again the platinum wire in the center of our growth cell provides a simple way to create a small droplet inside the solid matrix. The images of the equilibrium shape can then be processed with our digital image analysis system. Using Fourier analysis, we can then analyze the shape anisotropy very accurately as the results of Dougherty and Gollub in ammonium bromide have shown.^{33,34}

The shape of a two-dimensional crystallite in equilibrium with the surrounding melt (including anisotropic surface tension) is determined by the full Gibbs-Thompson equation³⁵

$$\bar{\Delta} = \frac{T_M}{L^2/C_p} (\gamma + \gamma_{\theta\theta}) \kappa \quad (3.14)$$

where: $\bar{\Delta}$ = dimensionless undercooling

L = latent heat of fusion

T_M = melting temperature

C_p = heat capacity

γ = surface tension

$\gamma_{\theta\theta}$ = second derivative of the surface tension with respect to the normal angle θ

κ = local curvature of the interface

(Note that some authors combine γ and $\gamma_{\theta\theta}$ into an effective $\gamma(\theta)$ as in Eq. (3.11).)

For a crystal with n -fold anisotropy, the surface tension takes the form:

$$\gamma = \gamma_0 (1 + \epsilon \cos(n\theta)) \quad (3.15)$$

Using Eq. (3.15) for the functional form of the surface tension in Eq. (3.14) we get:

$$\Delta = d_0 \kappa (1 - (n^2 - 1) \epsilon \cos(n\theta)) \quad (3.16)$$

For succinonitrile $n=4$, and the above equations can be used to calculate the theoretical equilibrium shape for varying undercoolings and different

values of anisotropy ϵ . Figure 3 shows a typical result obtained for $\epsilon = 0.05$.

We have made preliminary runs with one of our succinonitrile sample cells inside the new thermostat. A single crystal was formed in the melt. The shape of the resulting interface is shown in Figure 3. This interface shape was extracted from the digitized video image by using the software provided with our digital image analysis board. It is about five pixels wide. Computer programs are currently being developed to extract the precise interface shape parameters and to determine the anisotropy parameter ϵ from such data by fitting to Eq. (3.16).

3. The Role of Noise

During the analysis of our succinonitrile interface data shown in Appendix III, we noted that the Fourier transform of the interface profile (Fig. 3 of Appendix III) was extremely noisy. This led us to question the mechanism by which the initial instability evolves, assuming that random fluctuations present in the system provide the initial driving force.

This investigation, described in Appendix IV, was carried out by performing a computer simulation in which 38 Fourier amplitudes were allowed to evolve under the stochastic differential equation with random white-noise $f_k(t)$ added to the deterministic Mullins-Sekerka equation (see Eq. 3.8) where $\langle f_k(t)f_{k'}(t+\tau) \rangle = 2S_0^2 \delta(k-k')\delta(t)$. This procedure succeeded in reproducing the qualitative form of the Fourier spectrum, and also provided an estimate of the magnitude of the noise which must be present in the experiment to account for the observed pattern evolution: $S_0 = 3 \times 10^{-2} \mu\text{m}/\sqrt{\text{sec}}$.

Subsequently we carried out a theoretical analysis of the thermal noise which would be present by adding a Landau-Lifshitz random heat flux (characteristic of equilibrium fluctuations) to the integro-differential equation (3.11) for interface evolution.

The results of this analysis, to be reported in a future publication, were:

- (1) The Mullins-Sekerka dispersion relation (Eq. 3.4) is recovered.
- (2) The effect of including interface kinetics is not significant.
- (3) The resulting noise strength (for succinonitrile) is $S_0 = 1 \times 10^{-7} \mu\text{m}/\sqrt{\text{sec}}$ which is five orders of magnitude smaller than the value needed to explain the experiments, a result similar to that found for

$$T_m - T_i = 20\text{mK} \quad / \quad \epsilon = .05$$

Figure 3. Top: Theoretical equilibrium interface computed from Eq. (3.16) for $\epsilon=0.05$. $T_M-T_I=0.020\text{K}$. Thermodynamic parameters are for succinonitrile. Bottom: Experimental equilibrium interface of single succinonitrile crystal recorded by videomicroscopy.

the Rayleigh Benard instability by Meyer et.⁷
Analysis of other sources of noise is in progress.

4. Pattern Selection: Microscopic Solvability

Our preliminary study of the evolution of the planar interface instability, described in Appendix III, was primarily concerned with the early stages of pattern formation. However, we did obtain some results on the steady-state dendritic pattern as well. Again, the lack of a well defined undercooling prevented us from making a quantitative test of microscopic solvability, although we were able to test a theoretical prediction for the ratio of the dendrite tip radius to the dominant Mullins-Sekerka wavelength. These experiments will be continued during the next grant period with our new cylindrical cells as discussed in the following proposed experiments section

We have also implemented the computer program of Kessler, Koplik and Levine,¹⁷ (generously provided by H. Levine) in order to carry out our own calculations of velocity selection. Implementation of the program is somewhat delicate since, at convergence, the selected interface profile $y(x)$ that satisfies Eq. 3.11 with zero cusp amplitude typically departs from the Ivantsov parabola by a very small amount (on the order of 10^{-4} to 10^{-3} for succinonitrile). This program is now fully tested and will allow us to make numerical predictions for different materials.

To illustrate, we have computed the selected velocity for 2-dimensional dendrites as a function of the anisotropy parameter ϵ . The results are shown in Fig. 4. We have also superimposed straight lines indicating linear and $\epsilon^{2/3}$ behaviour which are the expected high- ϵ and low- ϵ behaviour found analytically by Barbieri et al.¹⁸

5. Directional Solidification

In Section IV we describe a new directional solidification apparatus which we constructed primarily for the study of sidebranching. We have also used this apparatus to explore other aspects of the pattern-forming instability in succinonitrile-acetone mixtures.

Figure 5 shows the evolution of the solidifying interface of succinonitrile containing less than 1% acetone in a directional solidification study performed recently in our lab. The sample cell is a sealed 50 μ m x 1000

Figure 4. Selected velocity vs anisotropy ϵ from numerical solution of Eq. (3.11). Thermodynamic parameters are those of succinonitrile.

a.

d.

b.

e.

c.

f.

Figure 5. Evolution of the interface of solidifying succinonitrile containing 1% acetone. Directional solidification at $V = 6\mu\text{m}/\text{sec}$.

~~SECRET~~

μm rectangular glass capillary tube, the temperature gradient was $-20^\circ/\text{cm}$, and the growth velocity was $6\mu\text{m}/\text{sec}$. The interface is shown at: (a) 0, (b) 60, (c) 100, (d) 120, (e) 240 and (f) 300 seconds after initiation of growth. The final tip radius (f) was $\rho \sim 6\mu\text{m}$ and the final interdendritic spacing $\sim 500\mu\text{m}$. Note how, during the coarsening phase, some dendrites are squeezed out, allowing the interdendritic spacing to increase.

Because the directional solidification geometry leads to a broadband instability, the wavelength selection process is very subtle and extremely nonlinear. One type of response to a perturbation recorded recently in our lab is shown in Fig. 6. Succinonitrile containing $<1\%$ acetone was undergoing directional solidification at $V = 2\mu\text{m}/\text{sec}$. The dendritic tip radius was $\rho = 12\mu\text{m}$. At $t=0$, the growth velocity was suddenly increased from $2\mu\text{m}/\text{sec}$ to $20\mu\text{m}/\text{sec}$. The figure shows the interface at (a) 0, (b) 39, (c) 48, (d) 51, (e) 75 and (f) 100 sec after the velocity increase. At $t=100$ sec, the tip radius has restabilized at $\rho \sim 4\mu\text{m}$.

Note how the interdendritic spacing has changed following the emergence of the narrow dendritic tip in (b). Tertiary dendrites, finding themselves in an "open" environment, grow rapidly and catch up with the original primary dendrite. As seen in (e) and (f), the final spacing is achieved by squeezing out some of the tertiaries, leaving an even row of equally spaced tips.

a.

d.

b.

e.

c.

f.

Figure 6. Response to a step increase in V from 2 to $20\mu\text{m}/\text{sec}$ during directional solidification of succinonitrile/acetone.

IV. SIDEBRANCHING

A. INTRODUCTION

Once a steady-state dendritic pattern has been reached during directional solidification or growth into a pure undercooled melt, the (nearly) parabolic dendrite tips continue to grow at constant velocity v , emitting continuous trains of sidebranches which grow and coarsen as they propagate down the dendrite. In the free growth geometry, these sidebranches remain nearly stationary in the laboratory frame.

Some aspects of dendritic sidebranching were studied experimentally by Glicksman and his coworkers^{10,16} and by Trivedi and his coworkers.²⁵ Recently, Dougherty et al have performed quantitative high-resolution videomicroscopy studies of free dendritic growth of ammonium bromide from saturated aqueous solutions.^{33,34} They found that $\sigma^* = 0.081 \pm 0.02$, in good agreement with Levine's numerical prediction from microscopic solvability theory $\sigma^* = 0.065 \pm 0.02$. These experiments revealed three major attributes of the sidebranching process:

- (i) The sidebranching is only roughly periodic, even quite close to the tip.
- (ii) There is little correlation between sidebranches on opposite sides of the tip
- (iii) The rms sidebranch amplitude is an exponential function of distance from the tip, with no apparent onset distance.

The theory of sidebranch formation has been discussed by several groups in the last few years, including Nittman and Stanley³⁶, and Langer, Pieters and their coworkers.^{2,37} A puzzle arose in this analysis in that the dendritic tip turns out to be linearly stable. However, the Langer-Pieters analysis, following methods developed by Zeldovich for flame fronts, revealed that localized wave packets generated by noise pulses near the tip grow in amplitude and stretch as they move down the dendrite, although at any point at a fixed distance down the tip, the disturbance dies out after the wave packet induced by the pulse has passed. This is the sense in which the front is stable even though the sidebranches continue to grow.

The growth of the sidebranch amplitude $A(s)$ with distance s from the dendrite tip was found to be²

$$A(s) = \exp \left[\frac{0.647}{(\sigma^*)^{1/2}} \left(\frac{s}{\rho} \right)^{1/4} \right] \quad (4.1)$$

Eq. (4.1) also explains, as noted by Langer, that at small anisotropy ϵ (where $\sigma^* \rightarrow 0$), the microscopic solvability theory will break down since the growth of the sidebranching instability will overwhelm the steady state solution.

This theory suggests that the sidebranching instability results from selective amplification of noise at the dendrite tip. Whether or not thermal fluctuations alone are sufficiently large to account for the observed sidebranches has not been conclusively established, although Langer's estimate indicates that they probably are not.²

Martin and Goldenfeld¹⁸ have carried out preliminary calculations in the 2-d boundary layer model of the sidebranching susceptibility to periodic heat pulses. They find that these questions could be addressed by imposing a pulsed heat perturbation at the tip, an experiment which we are currently setting up as discussed in the following section. Rabaud et al have performed a related (nonlocal) experiment by modulating the air pressure in a Saffman-Taylor fingering experiment.¹⁹ They found that such periodic forcing does generate a train of coherent sidebranches.

B. CURRENT RESEARCH

During the current grant period we have constructed and tested a microscope light-scattering spectrometer designed to collect scattered light from a region about $2\mu\text{m}$ in diameter. The instrument is based on a Nikon Diaphot inverted microscope equipped with a new temperature-gradient stage, a dc motor-driven directional solidification mechanism, optics for performing microprobe photon correlation spectroscopy, and a videocamera for performing image analysis studies. This instrument was used in the preliminary directional solidification experiments described in Sec. III. It will also be used in two new sidebranching experiments described in Section IVC: (1) a photon correlation spectroscopy study of the small-amplitude spontaneous shape fluctuations near the dendrite tip which presumably evolve into sidebranches, and (2) a videomicroscopy image analysis study of the response of sidebranching to periodic thermal tip perturbations.

This instrument utilizes a Spectra 124B 17mw He-Ne laser as the source. The laser beam is coupled to a single mode optical fiber (Corning Flexcor

633nm single mode) through a laser-fiber coupler (Newport High Precision Single Mode coupler F1015). At the other end of the optical fiber is a fiber-lens coupler in which a lens (focal length 6.4mm) focuses the light that comes out of the fiber to a spot of typically 4 μ m in diameter. This fiber-lens coupler is mounted on a XYZ manual translational stage so that we can position the focused laser spot with an accuracy of one micrometer anywhere on the sample.

The scattered light is collected by the objective lens of the microscope. The light in this microscope can be routed to the eyepieces and/or the video-camera port of the microscope. The microscope contains a special eyepiece (EG&G Gamma 700-10-36A 10x) in which a single optical fiber of 50 μ m core diameter is implanted to pick up the scattered light from the image plane conjugate to the specimen plane of the microscope. Since the fiber picks up the scattered light from an image already magnified by the objective and the eyepiece, a high spatial resolution can be achieved. Quantitatively, the size of the area from which the fiber picks up the light is equal to the physical cross-section of the pickup fiber divided by the magnification of the objective times the magnification of the eyepiece. For example, if a 10x objective is used, our pickup fiber with its 50 μ m diameter physical cross-section (core section) picks up light from an area of 0.5 μ m in diameter.

The eyepiece with the fiber is coupled to a fiber cable (EG&G Gamma 700-3B fiber optical probe) which transmits the light collected by the fiber in the eyepiece to a photomultiplier (Hamamatsu R629). At the other end of the fiber cable, a fiber-to-PMT (photomultiplier) tube coupling assembly is used. This home-made coupling assembly consists of a focal lens (focal length 50mm), a shutter and a laser light filter for filtering out the unwanted illumination light of the microscope.

The output signal of the PMT is routed either to an auto-correlator (Langeley Ford 1096) for measuring the intensity autocorrelation function, or to a Nicolet Scientific FFT Computing Spectrum Analyzer for direct spectral measurement. We have calibrated the instrument with polystyrene latex suspensions. Schematic diagrams of the optical and electronic layout of the spectrometer are shown in Fig. 7.

The temperature gradient stage has been designed for high-resolution directional solidification experiments. The stage consists of two blocks. The cold block is chilled by circulating constant temperature water from a water

M: motor driven linear driver for pulling the sample
 Proposed X, Y: X, Y motor driven translational positioner for probe light
 T: Time base corrector
 E: Video editing system for VCR

Figure 7. Schematic diagram of directional solidification sidebranching experiment. Top: Optical layout. Bottom: Overview of apparatus.

bath (NesLab Endocal Refrigerated Circulating Bath), and the hot block is heated by two cartridge heaters with a thermocouple feedback controller (Coler-Parmer Digi-sense). The temperature fluctuation of the cold and hot blocks is $\pm 10\text{mK}$. This setup is well suited for our directional solidification experiments in which a large steady heat current has to be maintained at all times. While a better temperature control system will be used in the future, the current setup is adequate to obtain the preliminary results for the succinonitrile-acetone system where the dominant mechanism is impurity diffusion. A diagram of the temperature gradient stage is shown in Fig. 3.

We have designed a sample cell assembly for these experiments in which the material under study is contained in a capillary tube (Vitro Dynamics Microslides) which is positioned in a window made of two microscope coverglasses. A diagram of the sample assembly is shown in Fig. 3. The capillary tube we used has a cross-section of $50\mu\text{m} \times 1000\mu\text{m}$ with the length available up to 4 feet. Although the capillary tube does not have optical quality surfaces, when we fill the space within the window with index matching paraffin oil, all the significant distortion due to the roughness of the capillary surface are eliminated. The window has a cross-section of $0.5\text{mm} \times 22\text{mm}$ to fit the very limited space under the microscope. The two open ends of the window are connected to two oil reservoirs. One reservoir has an open top through which the capillary tube is attached to a linear translation stage driven by a dc motor (Micro Mo 2251R012s1.5G-22/2-975:1, not shown in the figure). This open structure also prevents the window from cracking due to thermal expansion of the index matching oil during heating. The motor driven linear stage has a typical linearity of better than 0.1% at a pulling speed of $10\mu\text{m}$ per second.

Our sample assembly has the advantage of having a very long working length since the capillary tube is available in essentially unlimited lengths. Most experiments on directional solidification carried out by other groups use relatively short working length cells (2 or 3cm). Studies of directional solidification require achievement of a true steady state, which may not be reached by a system with a short working distance cell. Since one of our objectives is to study sidebranching in a growing steady state dendrite, the extra-long working length in our setup gives us a better chance of succeeding.

CELL ASSEMBLY

TEMPERATURE GRADIENT STAGE

Figure 8. Perspective view of sample assembly for directional solidification and sidebranching experiment. Top: Glass thermostat assembly. Bottom: Temperature gradient stage.

Sample preparation

Succinonitrile (SCN 99.6% pure) was purchased from Fluka. The SCN was further purified by multiple distillation, usually 4 times. In our distillation apparatus, a sample-loading flask is attached to the last stage of the apparatus, and the succinonitrile is loaded into a capillary sample tube in vacuum. This sample loading environment insures the cleanness of the sample, and it also prevents gas bubbles forming inside the tube, a nuisance often encountered in non-vacuum loading methods. The filled capillary tube was then taken out, and was sealed by a torch.

A sample of SCN at each stage of purification (after each distillation pass) was used to fill a capillary tube, and its interface evolution during directional solidification from an initially flat interface was observed. It is known that in an impure system there is a pulling velocity threshold for fixed temperature gradient beyond which a flat interface is unstable, and the interface will transform to a cellular or even dendritic form. We found that in our samples this threshold increases with each successive pass of distillation up to about 4 passes. After the 4th pass, we did not see the interface break up in a positive temperature gradient of 2K/mm with pulling speeds of up to 60 μ m/sec. This is in agreement with the theoretical prediction that the flat interface of a pure material in a directional solidification setup with positive temperature gradient is morphologically stable. We have taken advantage of this result in our other experiments to verify the purity of our samples.

Preliminary studies of sidebranching during directional solidification were performed with succinonitrile-acetone mixtures containing typically 1% acetone by weight added to succinonitrile purified by multiple distillation as described above. Samples were vacuum loaded into capillaries 50 μ m thick by 1000 μ m wide by 6cm long. (Preliminary observations of the interface evolution sequence in these samples are described in Section III.)

Preliminary light scattering experiments were performed with these samples. Figure 9 shows a single succinonitrile dendrite with a tip radius of $\sim 10\mu$ m illuminated by a red He-Ne laser beam (which appears yellow in the photograph). Laser light scattered from the dendrite has been detected, but so far we have not been successful in obtaining autocorrelation data due to excessive elastic scattering from the glass surfaces of the cell. We are

Figure 9. Photograph of steady state succinonitrile dendrite with $4\mu\text{m}$ diameter helium-neon laser beam incident at the tip.

- 18 -

currently rebuilding the external housing of the spectrometer in order to reduce dust and elastic scattering.

We have also begun the tip perturbation experiment by positioning an electronic shutter activated by a pulse generator between the laser and the fiber optic coupler. The laser is used here as a perturbing heat source localized at the tip. In our preliminary runs, we used a He-Ne laser (Spectra 124B) and an electronic shutter controlled by a pulse generator to regulate the frequency at which the laser heats the tip.

Preliminary runs showed that 10mW of red light can significantly retard the tip growth relative to an unperturbed dendrite in the same run. Therefore a perturbation of this kind is readily feasible. We will also try using a 2-watt argon ion laser to increase the size of the perturbation.

V. LIGHT SCATTERING AT THE CRYSTAL-MELT INTERFACE

A. INTRODUCTION

Since the discovery over ten years ago by Bilgram, Guttinger and Kanzig of quasielastic light scattering at the growing ice-water interface, this phenomenon (or phenomena) has been observed in a total of seven different materials (as shown in Table I) in experiments performed at the ETH-Zurich¹⁻³, City College of New York^{4,5}, the University of California-Davis⁶⁻⁸, the University of Minas Gerais (Brazil)⁹⁻¹¹ and the CNET laboratory in France.¹² In contrast to the inelastic light scattering observed on the crystal side of the interface in salol^{13,14,15} which is known to result from Doppler-shifted scattering from the advancing ledges of polygonized screw dislocations, the

TABLE I

Diffusion Coefficients and Equivalent Radii from Boundary Layer Light Scattering

MATERIAL	D Diffusional Coefficient (cm ² /sec)	R Radius μ m
Biphenyl(a)	$4.9 \times 10^{-10} - 1.5 \times 10^{-9}$	1.0 - 3.6
Cyclohexane(b)	6×10^{-9}	0.26
Cyclohexanol(c)	$2 \times 10^{-11} - 9 \times 10^{-11}$	0.34 - 1.5
Naphthalene(a)	$1.6 \times 10^{-10} - 1.3 \times 10^{-9}$	1.7 - 3.2
Salol a-axis(d)	$7.5 \times 10^{-10} - 1.25 \times 10^{-9}$	0.22 - 0.36
a-axis(e)	$0.6 \times 10^{-10} - 1.0 \times 10^{-10}$	2.7 - 4.5
b-axis(e)	$1.0 \times 10^{-10} - 1.0 \times 10^{-9}$	0.27 - 2.7
b-axis(f)	$2.3 \times 10^{-12} - 7.8 \times 10^{-10}$	0.35 - 117.0
Succinonitrile(g)	$1.5 \times 10^{-9} - 3.0 \times 10^{-9}$	0.6 - 1.2
degassed(g)	$2.9 \times 10^{-11} - 6.9 \times 10^{-11}$	31.0 - 52.0
Water a-c axis(h)	$1.5 \times 10^{-11} - 3.0 \times 10^{-9}$	0.3 - 65.0
c-axis(i)	$1.4 \times 10^{-9} - 5.7 \times 10^{-9}$	0.014 - 0.079
c-axis(h)	$4.5 \times 10^{-9} - 6.3 \times 10^{-9}$	0.059 - 0.072

- a. O.N. Mesquita, L.O. Ladeira, I. Contijo, A.G. Oliveira and G.A. Barbosa, Phys. Rev. B 38, 1550 (1988).
- b. R. Steininger and J. Bilgram, Helv. Phys. Acta 62, 215 (1989).
- c. G. Livescu, M.R. Srinivasan, H. Chou and H.Z. Cummins, Phys. Rev. A 36, 2293 (1987).
- d. U. Durig, J.H. Bilgram and W. Kanzig, Phys. Rev. B 30, 946 (1984).
- e. O.N. Mesquita and H.Z. Cummins, Physico-Chemical Hydrodynamics 5, 389 (1984); O.N. Mesquita, D.G. Neal, M. Copic and H.Z. Cummins, Phys. Rev. B 29, 2846 (1984)..
- f. L. Williams and H.Z. Cummins (in preparation).
- g. J.M. Laherrere, H. Savary, R. Mellet and J.C. Toledano, (submitted to Phys. Rev. A, August 1989).
- h. J.P. Vesenska and Y. Yeh, Phys. Rev. A 38, 5310 (1988).
- i. P. Boni, J.H. Bilgram and W. Kanzig, Phys. Rev. A 28, 2953 (1983).

~~34~~

origin of the relaxational light scattering observed on the fluid side of the interface in all the materials shown in Table I has been a matter of considerable controversy.

The basic properties of this scattering phenomenon, as revealed by the experiments, are:

a) It occurs in a fluid boundary layer at least several microns in thickness and co-exists with the translational dynamics on the crystal surface.

b) It is stronger than scattering from either the crystal surface or the bulk fluid.

c) It requires a delay time on the order of a few hours to begin.

d) The intensity correlation function of the scattered light is approximately exponential with a polydispersity that varies from a negligibly small value at onset to a value on the order of unity after prolonged growth.

e) It occurs on both atomically smooth and rough interfaces.

f) The effective diffusion constant D is typically 10^4 times smaller than the self-diffusion coefficient, and 10^6 times smaller than the thermal diffusion coefficient.

Several models have been proposed to explain the origin of this anomalous scattering:

a) Capillary waves on the interface (Bilgram et al).⁶¹

b) Diffusion of defects in the surface (Keizer et al).⁶²⁻⁷⁰

c) Partial orientation of molecules in the liquid layer adjacent to the interface (Mesquita et al).³⁴

d) Dynamic roughening (van Saarloos and Gilmer).⁷¹

e) A new mesophase (Boni et al).³⁰

f) Gaseous microbubbles (Cummins et al).³⁰

Models (a) - (d) are now generally regarded as inconsistent with the experimental data, particularly the observed thickness of the scattering layer which increases with decreasing growth velocity.³³ Thus the mesophase model³⁰ and the gaseous microbubble model³⁰ are currently the only explanations consistent with the basic properties given above.

We proposed the microbubble model in 1986 after studying the dependence of the scattered intensity $I(\theta)$ on the scattering angle θ in salol.³⁰ This study showed that $I(\theta)$ decreases too rapidly with increasing θ to be described

- 32 -

by an Ornstein-Zernike form characteristic of thermodynamic density (or entropy) fluctuations, but could be fit with a Mie scattering function for spheres of the size indicated by the effective diffusion constant deduced from the correlation function. In contrast to this result, Guttinger et al had shown that for water there is no apparent angular dependence of the scattered intensity⁴², and very recently, Steininger and Bilgram³³ measured the angular dependence of the scattered intensity for cyclohexane and found that their data fit the Ornstein-Zernike form but not the Mie form!

Our microbubble model is based on the assumed existence of dissolved gaseous impurities in the melt. The resulting buildup of gas concentration in the fluid boundary layer during solidification, due to solute rejection, can reach a level sufficient to allow heterogeneous bubble nucleation to occur. We note that gas bubble nucleation at the crystal-melt interface is a well-established phenomenon which had already been extensively studied, especially in the Soviet Union.⁷² As noted by Geguzin and Dzuba⁷², the characteristic width of the high solute concentration layer in the melt is $\delta = D/V$ where D is the diffusion constant of the impurity in the melt and V is the growth velocity. The $1/V$ thickness of the interface layer predicted by this relation was observed in scattering from the ice-water interface by Halter et al.³⁴ Nevertheless, Bilgram has objected to the microbubble model both because of the small theoretical bubble nucleation rate³² and because of his observed $I(\theta)$ for cyclohexane.³³ Bilgram maintains that the observed dynamic light scattering is due to entropy fluctuations in a mesophasic boundary layer with properties intermediate between crystal and liquid, with a very large isothermal compressibility.

Mazur and Keizer⁴⁹, and Vesenka and Yen⁴³ suggested that there might be two different scattering phenomena involved, one for the c face of ice, and microbubbles for all other systems. However, the $I(\theta)$ observations for cyclohexane reported by Steininger and Bilgram³³ show that this compromise explanation is not possible. Therefore, a complete explanation of the boundary layer scattering phenomenon does not yet exist.

Nevertheless, there is considerable evidence for the gaseous microbubble model, at least in some materials. As we will discuss in the following section, we have observed that over a long growth cycle (~14 days) the bubble size increases monotonically until bubbles are eventually trapped by the

advancing interface and can be photographed.⁶⁰ We also observed that after two days of continuous pumping on the salol growth tube, the scattering disappeared. Recently, Laherrere et al have investigated boundary-layer scattering in succinonitrile.⁶¹ They found that after ten cycles of solidification while pumping, the scattering disappeared and subsequently reappeared weakly with an increase of ~40 in the apparent radius. Vasenka and Yeh⁶² have investigated the effects of adding helium or argon gas to the water, and found dramatic changes in the observed correlation functions including increases in both bubble size and polydispersity.

Additional evidence for microbubbles is provided by the observation of a "lift-off layer". When growth is stopped after scattering has begun and the crystal is melted back (by reversing the motor drive), the scattering layer is observed to remain stationary in the melt as the interface moves away. This effect was seen in water by Vasenka and Yen^{62,63} and by Halter et al.⁶⁴, and in cyclohexanol by Livescu et al.⁶⁵. Note that the long persistence time of the lift-off layer and its observed gradual spreading with time⁶⁴ can be understood as a consequence of the very small diffusion constants of the bubbles.

Mesquita et al⁶⁶ studied dynamic light scattering in biphenyl and naphthalene, with emphasis on the initial onset of scattering. They noted that the approximate time-dependent solution to the diffusion equation

$$\frac{C_1}{C_0} = 1 + \left(\frac{1-k}{k}\right) \left\{ 1 - \exp\left[1 - \frac{v^2(1-k)kt}{D}\right] \right\} \quad (5.1)$$

when linearized becomes

$$\frac{C_1}{C_0} = 1 + \frac{v^2(1-k)^2}{D} t = 1 + \frac{v^2}{D} t \quad (5.2)$$

when C_1 and C_0 are the dissolved gas concentrations at the interface and in the melt far from the interface, k is the partition (or segregation) coefficient, v is the growth velocity, and D is the diffusion constant of the dissolved gas.

For bubbles of radius R to exist in (unstable) equilibrium at the interface, the concentration must be⁶⁶

$$\frac{C_1}{C_0} = 1 + \frac{2\sigma}{pR} \quad (5.3)$$

where p is the fluid pressure and σ is the surface tension. Equating (5.2) and (5.3), the following scaling law is found:⁶⁶

$$Rt = \frac{2\sigma D}{p} \frac{1}{v^2} \quad (5.4)$$

Mesquita et al measured the bubble size at onset R and the onset time t for different growth speeds v in biphenyl and naphthalene and found for each material that the product $R \cdot t$ is proportional to v^{-2} as predicted by Eq. (5.4).

B. CURRENT RESEARCH

During the current grant period we have performed studies of the long-time evolution of boundary layer light scattering in salol. By using a slow growth velocity we have been able to follow the growth of one crystal for a period of up to 14 days and have seen the bubble size increase from an onset radius of the order of $1 \mu\text{m}$ to a final radius of roughly $100 - 200 \mu\text{m}$ as illustrated in Figure 10.

On two occasions the bubbles have grown large enough to be trapped. Upon trapping a layer of bubbles, we have allowed the crystal to solidify completely and then removed it from the thermostat and examined it under a microscope. This permitted us to obtain the first direct visualization of the microbubbles. A photograph is shown in Fig. 11. We were also able to directly measure the radius of the bubbles and test the scaling dependence of particle size vs growth velocity for the capture of inclusions found by Chernov and Temkin.⁷³ At a growth velocity of $\sim 0.212 \mu\text{m}/\text{sec}$ we observed trapped bubbles with radii in the range $50 - 100 \mu\text{m}$, which is consistent with the radius we had obtained from light scattering. The radius was also consistent with Chernov and Tempkin's survey, as shown in Fig. 12.

It was also noted that changing the temperature gradient and growth velocity had a marked effect on the rate of increase of the bubble size. If we compare Fig. 10 with Fig. 13, where the temperature gradient was lowered from $1.1^\circ\text{C}/\text{cm}$ to $0.45^\circ\text{C}/\text{cm}$ and the growth velocity was increased from $.0847 \mu\text{m}/\text{s}$ to $.212 \mu\text{m}/\text{s}$, we can clearly see that the rate of increase of the bubble size with time is larger in the second case. If one considers the forces on the bubbles this is to be expected. A higher growth velocity will increase the Stokes force pushing the bubbles towards the interface, and a lower temperature gradient will decrease the thermocapillary force which tends to pull the bubble away from the interface. These two changes will result in bubbles that spend a longer time in the supersaturated region around the interface, and will thus grow faster. However, this experiment still

Figure 10. Radius of bubbles in salol extracted from dynamic light scattering vs. time after growth was initiated. Growth velocity $V = 0.0847 \mu\text{m}/\text{sec}$. Temperature gradient $G = 1.1^\circ \text{C}/\text{cm}$.

Figure 11. Photograph showing bubbles that have been trapped in salol by the advancing crystal interface.

Figure 12. Critical growth rate for trapping an inclusion vs radius of inclusion. A summary of experimental data and theoretical curves from A.A. Chernov and D.E. Temkin.⁷³ The large star represents the bubbles that were trapped in our salol experiment.

requires repeating to check for the effect of the gas concentration in the melt.

We have also performed an analysis of the forces on the bubbles assuming that the three main forces are the viscous Stokes force $F_V = 6\pi\eta R V$, the thermocapillary force $F_T = -4\pi R^2 \frac{d\sigma}{dT} G$, and the buoyancy force $F_B = \frac{4\pi}{3} R^3 \rho g$ where G is the temperature gradient. If these three forces are in equilibrium ($F_T + F_V + F_B = 0$) the bubble will be carried along ahead of the interface.

This equilibrium bubble radius can then be plotted as a function of velocity for the relevant temperature gradients (i.e. those actually used in the experimental work). We have done this for ice and salol (see Fig. 14), and on the same graph have plotted the range of data points for the initial radius and growth velocity obtained in experiments here and in Switzerland. The agreement is seen to be quite good.

We have also performed experiments where we connected our sample to a vacuum system and pumped on the sample during growth, and observed the scattering disappear. We have seen the intensity of scattering reduced with repeated passes of crystal growth in the Bridgmann configuration in a closed sealed tube. This is assumed to occur because the gas in the nucleated bubbles does not get fully reabsorbed into the melt.

We have also tried to repeat Mesquita's experiments⁶⁶ for the onset of scattering in salol, but have found that at the temperature gradient we are using the time for the crystal to reach its equilibrium velocity is much greater than the time for the onset of scattering. Thus the onset of scattering is so gradual that it is impossible to consistently define the onset time and radius. We are currently performing a series of experiments at a higher temperature gradient in which the crystal will reach its equilibrium velocity faster. If we are still unable to adequately define our onset radius and time, we intend to switch to succinonitrile, as discussed in the following proposed experiments section.

(Appendices removed and
cycled separately -)

END

**DATE
FILMED**

4 / 03 / 92