Final Report

**DOE/PC/79909-T3
(DE92004845)**

**PYRITE THERMOCHEMISTRY, ASH AGGLOMERATION, AND CHAR
FRAGMENTATION DURING PULVERIZED COAL COMBUSTION**

Final Technical Report

**By
Anieflok Akan-Etuk
Ruben Diaz
Stephen Niksa
Sayeed Akhtar**

October 1991

Work Performed Under Contract No. FG22-87PC79909

**For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

**By
Stanford University
Stanford, California**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**PYRITE THERMOCHEMISTRY, ASH AGGLOMERATION, AND CHAR
FRAGMENTATION DURING PULVERIZED COAL COMBUSTION**

Final Technical Report
Grant DE-FG22-87PC79909

DOE/PC/79909--T3
DE92 004845

Prepared for
The United States Department of Energy
Sayeed Akhtar
Project Officer
Pittsburgh Energy Technology Center
Pittsburgh, PA 15236

Submitted by
Mssrs. Aniefiok Akan-Etuk and Ruben Diaz
and Assistant Professor Stephen Niksa

October 1991

High Temperature Gasdynamics Laboratory
Department of Mechanical Engineering
Stanford University

TABLE OF CONTENTS

<u>Chapter</u>	<u>Page</u>
TABLE OF CONTENTS	i
LIST OF TABLES	iv
LIST OF FIGURES	v
CHAPTER 1: INTRODUCTION	1
1.1 Problem Statement	1
1.2 Review of Related Work.	2
1.3 Unresolved Issues.	4
1.4 Scope of Present Study.	6
CHAPTER 2: MATERIALS.	8
2.1 Introduction	8
2.2 Pyrite Inclusions.	9
2.2.1 Introduction	9
2.2.2 Size Classification of Pyrite by Wet Sieving	10
2.2.3 Size Classification of Pyrite by Sedimentation	11
2.2.4 Measured Size Distribution of Inclusions	14
2.2.5 Parametric Study of Sedimentation Procedure	18
2.2.6 Pyrite Inclusions for Production Chars.	20
2.3 Extraneous Pyrite	22
2.3.1 Introduction	22
2.3.2 Size Classification of Pyrite by Dry Sieving	23
2.3.3 Double-Stage Size Classification: Dry Sieving-Wet Sieving.	25
2.4.4 Size Classification of Production Extraneous Pyrite: Sedimentation-Wet Sieving	26
2.4 Char Synthesis Procedure	28
2.4.1 Introduction	28
2.4.2 General Description.	28
2.5 Glassy Carbon	31
2.6 Macroporous Char.	34
2.6.1 Introduction	34
2.6.2 Introducing Macrovoids into Synthetic Carbons	35

2.7	Non-Porous Pyrite-Loaded Char	38
2.7.1	Introduction	38
2.7.2	Introducing Pyrite Inclusions into the Carbons	38
2.8	Macroporous Pyrite-Loaded Char.	40
2.9	Centrifugation Procedure.	41
2.9.1	Motivation	41
2.9.2	Density Classification Based on Centrifugation	42
2.9.3	Density Classification to Control the Pyrite Loading	45
2.9.4	Density Classification to Control the Dispersion of Macrovoids.	50
2.9.5	Density Classification to Control Both Pyrite Loading and Macrovoidage.	53
2.10	CHN-Ashing Analysis	56
2.11	Production Chars	59
2.11.1	Non-Porous Pyrite-Loaded Char	59
2.11.2	Macroporous Pyrite-Loaded Char	61
CHAPTER 3: RADIANT SUSPENSION FLOW REACTOR		65
3.1	Introduction.	65
3.2	Reactor Description	66
3.2.1	Overview.	66
3.2.2	The Particle Feeder.	66
3.2.3	The Inductively-Heated Radiant Furnace	69
3.2.4	The Virtual Impactor.	70
3.2.5	Reactor Performance in Coal Pyrolysis	71
3.3	Particle Temperatures and Parametric Sensivity	73
3.4	Operating Conditions for Oxidation Studies.	77
CHAPTER 4: X-RAY DIFFRACTION ANALYSIS.		80
4.1	Introduction.	80
4.2	An Overview of X-Ray Diffraction Analysis	81
4.3	Peak Assignments.	82
4.4	Sample Preparation	85
4.4.1	Carbon-Free Sample	85
4.4.2	Carbonaceous Samples.	85
4.5	Intrinsic Standard Method of Calibration	89
4.6	Adopted X-Ray Diffraction Scheme	94
4.7	New XRD Analysis System	96
4.7.1	Calibration of Iron Sulfide Phases	96
4.7.2	New X-Ray Diffraction Scheme	96

CHAPTER 5: THERMOCHEMICAL CALCULATIONS.	101
5.1 Introduction.	101
5.2 The Modified STANJAN Simulator.	101
5.3 Comparisons with High Temperature Iron Oxide Ash Thermochemistry	102
5.4 Convergence and Specification of the Product Phases	108
5.5 The Pyrite Phase Diagram	110
5.6 Baseline Information	111
5.6.1 Pyrite Pyrolysis	111
5.6.2 Pyrite Oxidation	112
CHAPTER 6: RESULTS AND DISCUSSION.	114
6.1 Introduction.	114
6.2 Experimental Results	115
6.2.1 Physical Description of Ash	115
6.2.2 Quantitative X-Ray	119
6.2.3 Kinetic Rate Parameters for Pyrite Pyrolysis	123
6.3 Discussion.	129
APPENDIX A: FOULING AND SLAGGING.	131
A.1 Introduction.	131
A.2 Types of Discussion.	132
A.3 Sticky Alkalinity.	133
A.4 Sticky Alkaline Chemical Reactions	134
A.5 Reactions of Iron-Bearing Minerals.	135
REFERENCES.	138

LIST OF TABLES

<u>Table</u>	<u>Page</u>
2.1 Calculated Settling Velocity of Pyrite in Water	101
2.2 Weight Loss of Polymer/Acetone at Various Stages of Char Synthesis	101
2.3 Specific Gravity of Solutions of Percut in Perchloroethylene.	102
2.4 Char Specific Gravity for Various Pyrite Loadings and Densities of the Char Matrix.	108
2.5 Fraction of Initial Pyrite Remaining after Various Stages of Char Processing	110
4.1 Calibration Equations for X-Ray Diffraction Analysis (relative concentration, c, as function of relative intensity, I)	111
4.2 Intrinsic Standard Determinations of Composition of Synthetic Mixtures	1
4.3 Internal Standard Determinations of FeO Content of Synthetic Mixtures	102
4.4 Intrinsic Standard Determinations of Fe_{1-x}S Content of Synthetic Mixtures.	
5.1 Pyrite Phase Diagram Duplication (STANJANR results followed by pyrite phase diagram data in parenthesis).	108
6.1 Measured and Calculated Residence Times	138
6.2 Measured and Calculated Gas Yields.	129

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
2.1 Mass-based cumulative distribution of pyrite obtained from American Minerals, after grinding, but before size classification.	15
2.2 The mass-based cumulative distributions from two attempts to recover pyrite inclusions under 4 microns from the raw grind using sedimentation. Reproducibility is evident in the replicate distributions	16
2.3 Comparison of sedimentation scheme for size classification that ultrasonicates particles as they are settling (solid curve) with one that ultrasonicates particles before they settle (dotted curve).	16
2.3 Comparison of effectiveness of two size classification schemes: sedimentation (solid curve) and wetsieving (dotted curve). Plotted are mass-based cumulative distributions from attempts to obtain particles in the range of 4 to 8 microns	17
2.5 Comparison of size distributions of 2 to 5 micron pyrite obtained by sedimentation with (solid curve) and without (dotted curve) pregrinding.	19
2.6 Comparison of size distributions of 2 to 5 micron pyrite obtained by sedimentation when the upper cutoff is addressed first (dashed curve) and when it is addressed last (solid curve). The initial distribution is represented by the dotted curve.	19
2.7 Size distributions showing that the quality of 2 to 5 micron class obtained by sedimentation improves as the concentration of pyrite in the suspension increases. Also indicated are the number of times the suspensions were decanted to obtain the upper cutoff	20
2.8 Mass-based cumulative size distribution of pyrite inclusions for production chars.	21
2.9 Mass-based cumulative size distribution of -100 mesh (-150 microns) pyrite obtained from Alfa Chemicals. Note that the particles are an order of magnitude smaller than the advertised size	23
2.10 Comparison of effectiveness of RoTap (solid and dotted curves) and sieve shaker (dashed curve) for obtaining 38-to-45 micron size class of pyrite. These are mass-based size distributions of the samples showing incremental changes induced by each round of classification	24
2.11 Effect of sieving time and initial pyrite loading on the quality of the size distribution of pyrite in sieve shaker's 38-to-45 micron size class. Neither sieving time nor pyrite loading affects the size distribution.	25
2.12 Effectiveness of wet-sieving (dashed curve) on the size distribution of pre-classified pyrite (solid curve). The pyrite was washed on a 38 micron screen after it was extracted from the sieve shaker's 38-to-45 micron class.	26
2.13 Mass-based cumulative size distribution of production extraneous pyrite (solid curve compared with that obtained using the Ro-Tap (dotted curve).	27

Figure	Page
2.14 (A) SEM micrograph at 2440X of an individual, 100 micron carbon particle synthesized from furfuryl alcohol. (B) Cross-section micrograph at 1250X of synthetic carbon ground into the pulverized fuel grade, without any size classification	32
2.15 Mass-based cumulative size distribution of lycopodium powder.	36
2.16 Cross-section micrograph at 1250X of a 100-micron synthetic carbon particle with 16-micron pores	37
2.17 (A) Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions, from top of synthesis vessels. (B) Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions, from bottom of synthesis vessels.	39
2.18 Cumulative and differential density distributions of the synthetic char matrix. The density distributions were obtained by ultracentrifuging non-porous, mineral free char in solvents with tightly controlled specific gravities	47
2.19 Cumulative and differential density distributions of nonporous char synthesized to have 10% pyrite loading. The density distributions were obtained by ultracentrifuging in liquids of various specific gravities	48
2.20 Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions. (A) Specific gravity of 1.26 to 1.28. (B) Specific gravity of 1.30 to 1.32.	49
2.21 Cumulative and differential density distributions of mineral-free char synthesized to have 75% porosity. The density distributions were determined by ultracentrifuging char in fluids of controlled specific gravity.	51
2.22 Cross-section micrograph at 100X of 65-175 micron particles of highly porous synthetic carbon. (A) Specific gravity of 1.16 to 1.18. (B) Specific gravity of 1.26 to 1.28.	52
2.23 Cumulative and differential density distributions of char synthesized to have 50% porosity and 10% pyrite loading. The density distributions were obtained by ultracentrifuging char in fluids with controlled specific gravities.	54
2.24 Cross-section micrograph at 250X of 100-micron particles of highly porous synthetic carbons with pyrite inclusions. (A) Specific gravity of 1.26 to 1.28. (B) Specific gravity of 1.30 to 1.32.	55
2.25 Basis for calibration factors for relating amount of pyrite remaining after ashing in the elemental analyzer to initial amount of pyrite in synthetic carbon. plotted is the fraction of initial pyrite lost during ashing for various values of initial pyrite content of a synthetic carbon/pyrite mixture	57
2.26 Cumulative and differential density distributions of non-porous char synthesized to have an average loading of 12%. The density distributions were obtained by ultracentrifuging char in liquids of various specific gravities.	57

Figure	Page
2.27 Comparison of the pyrite loading obtained by CHN-ashing with the values calculated on the basis of char density for the different classes of the sample synthetic char.	58
2.28 Mass-based cumulative size distribution of non-porous production char. The nominal size class is 90 to 106 microns.	60
2.29 Cross-section micrograph at 625X of non-porous production char. Shown are 100 micron char particles with 2 to 5 micron pyrite inclusions.	61
2.30 Mass-based cumulative size distribution of porous production char. The nominal size class is 90 to 106 microns	62
2.31 Cross-section micrograph at 625X of macroporous production char. Shown are 100 micron char particles with 28 micron pores and 2 to 5 micron pyrite inclusions.	63
2.32 Cross-section micrograph at 250X of macroporous production char. Shown are 100 micron char particles with 28 micron pores and 2 to 5 micron pyrite inclusions.	64
3.1 The radiant suspension flow reactor	67
3.2 The particle feeder.	68
3.3 The inductively-heated radiant furnace.	70
3.4 The virtual impactor.	71
3.5 Total (OPEN symbols) and aerosol yield (FILLED symbols) for Illinois #6 coal, 75-106 μm , diamond 1840K, inverted triangle 1680K, triangle 1570K wall temperature, 400 particles/cc.	72
3.6 Calculated particle (solid curves) and gas (dashed curves) temperature histories in the radiant suspension flow reactor for various suspension loadings. The suspension consists of coal in a 4 slm flow of nitrogen at a furnace temperature of 1600K.	74
3.7 Calculated particle (solid curves) and gas (dashed curves) temperature histories in the radiant suspension flow reactor for various emissivities of pyrite. The suspension consists of 39000 particles/ cm^3 of pyrite in a 3.9 slm flow of argon at a furnace temperature of 1260K.	75
3.8 PYRTEMP calculated ordered pairs of frequency factor and activation energy for various emissivities and the following conditions: $V_{\text{cr}} = 50 \text{ cm/sec}$, feed rate = 0.54 g/min, $T_w = 1626\text{K}$ and outlet yield of 53.3%.	76
3.9 Calculated char diameter in O_2 -Ar flow through a quartz tube added to the exit of the radiant furnace. At the inlet, the suspension temperature is 1550K; the tube wall remains at 300K.	78
4.1 X-ray diffraction pattern from a mixture of iron compounds and pulverized synthetic carbon. The mixture composition is 8% Fe_{1-x}S (P), 5% FeO (W), 29% Fe_3O_4 (M), 6% Fe_2O_3 (H), and 52% C (C).	83

Figure	Page
4.2 X-ray diffraction pattern from a mixture of FeS , FeS_2 , FeO , Fe_2O_3 , and Fe_3O_4 . Labelled are only those peaks that are used for quantitative determinations of composition.	84
4.3 X-ray diffraction pattern of 63 to 125 micron char of 10% pyrite loading. The mineral peaks are indistinguishable from the carbon background.	86
4.4 X-ray diffraction pattern of 63 to 125 micron char of 10% pyrite loading after mild pulverization (1X at 2 tons, followed by 2X at 5 tons). Note the Fe_{1-x}S peaks at 2θ values of 30, 34, 44, and 53 degrees	87
4.5 X-ray diffraction pattern of 63 to 125 micron char of 15% pyrite loading after intense pulverization (2X at 15 tons). Note the Fe_{1-x}S peaks at 2θ values of 30, 34, 44, and 53 degrees.	87
4.6 Mass-based cumulative size distribution of 90 to 106 micron glassy carbon after grinding. Hand grinding with mortar and pestle (solid line) is compared with pulverization at 15 tons for 4X (dotted line).	88
4.7 Concentration of FeO for various x-ray diffraction intensities, relative to Fe_{1-x}S (solid curve) and Fe_3O_4 (dotted curve)	90
4.8 Intrinsic standard calibration curves for x-ray diffraction analysis of extraneous pyrite. Shown are curves for Fe_{1-x}S (square), FeS_2 (triangle), Fe_2O_3 (circle), and Fe_3O_4 (diamond) relative to Fe_{1-x}S (solid curves) and Fe_3O_4 (dotted curves). Cubic polynomials are used for all fits.	90
4.9 X-ray diffraction calibration curve for various $\text{FeS}_2:\text{Fe}_{1-x}\text{S}$ ratios	93
4.10 Powder diffraction scan of pyrite (40 kV 20 mA).	97
4.11 43° diffraction peak of pyrrhotite (40 kV 20 mA)	97
4.12 53° diffraction peak of pyrrhotite (40 kV 20 mA)	98
4.13 X-ray diffraction calibration curve: pyrrhotite to pyrite.	98
4.14 X-ray diffraction calibration curve: pyrite to pyrrhotite.	99
5.1 Calculated equilibrium iron phase percentages as a function of oxygen level at 1300K (from Huffman, original)	102
5.2 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1000K. (Symbols = STANJANR, lines = Huffman)	104
5.3 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1300K. (Symbols = STANJANR, lines = Huffman)	104
5.4 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1500K. (Symbols = STANJANR, lines = Huffman)	105
5.5 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1800K. (Symbols = STANJANR, lines = Huffman)	105
5.6 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1300K (all condensates considered)..	106

Figure	Page
5.7 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1000K (all condensates considered).....	107
5.8 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1800K (all condensates considered).....	107
5.9 Pyrite phase diagram [25].	109
5.10 STANJANR calculated equilibrium iron phase percentages as a function of temperature (pyrite pyrolysis).	111
5.11 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 2.14 O ₂ /FeS ₂	112
5.12 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 3.58 O ₂ /FeS ₂	113
5.13 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 7.16 O ₂ /FeS ₂	113
6.1 Cross-section photomicrographs of unreacted pyrite particles. (A) 500X magnification, establishing interparticle uniformity. (B) 1250X magnification, establishing intraparticle uniformity.	116
6.2 Cross-section photomicrographs at 500X of pyrite particles after inert pyrolysis at 1610K. (A) Nominal residence time of 370 ms. (B) Nominal residence time of 725 ms	117
6.3 Cross-section photomicrographs at 500X of pyrite particles after oxidative pyrolysis for nominal residence time of 725 ms. (A) Furnace temperature of 1500K. (B) Furnace temperature of 1610K	118
6.4 Weight fraction of Fe _{0.877} S in pyrolysis products at various wall temperatures, 3.9 slm Ar, 0.8g FeS ₂ /min	119
6.5 Weight fraction of Fe _{0.877} S in pyrolysis products at various cold gas residence times, 1610K wall temperature, 0.8g FeS ₂ /min	120
6.6 Fractional mass loss of the solid phase at various flow velocities for a wall temperature of 1626K and a nominal number density of 12,000#/cc.	121
6.7 Mass fraction of Fe _{0.877} S in condensed pyrolysis products at various flow velocities for a wall temperature of 1626K and a nominal number density of 12,000 #/cc.	122
6.8 Weight fraction of Fe _{0.877} S in oxidative pyrolysis products at various wall temperatures, 3.9 slm of 6% O ₂ -Ar, 0.67g FeS ₂ /min	123
6.9 % Original Weight Loss of Pyrite versus Temperature for a Dial Heating Rate of 5.0°C/min.. . . .	125

6.10	X-Ray Scan of Pyrite Pyrolysis Product (40kV 20mA).	125
6.11	Modified Arrhenius Diagram for Two Heating Rates.	126
6.12	Fractional Yield During Heat-up.	127
6.13	Comparison of Experimentally Observed (solid curve) and Calculated Equilibrium (dotted curve) Weight Fraction of $\text{Fe}_{0.877}\text{S}$ at Various Wall Temperatures. Conditions are Inert Pyrolysis, 3.9 slm Ar, 0.8g FeS_2 /min.	130

CHAPTER ONE

INTRODUCTION

1.1 PROBLEM STATEMENT

The use of coal as an energy source poses several technological problems. Among the most prominent of these problems is the formation of molten deposits and subsequent corrosion of steam tubes by mineral matter during pulverized fuel firing. This problem, referred to as fouling and slagging, is responsible for millions of dollars of losses each year. Fouling and slagging is so costly because it severely limits the performance, reliability, and efficiency of power plants. The mineral deposits on the tube walls impede heat transfer and cause corrosion. When enough deposits accumulate, they may also fall and cause mechanical damage.

Among the mineral species most strongly implicated in fouling and slagging is iron pyrite (FeS_2) [1]. The sulfur in pyrite causes corrosion through both solid-phase sulfidation of heat-receiving surfaces by impinged particles and external corrosion by effluent sulfur gas. In addition, pyrite derivatives lower the viscosity of any molten slag formed in the furnace. Furthermore, pyrite particles captured on the hearth can accumulate as a pool of molten sulfides that lead to mechanical failure of the furnace bottom.

Perhaps, the most important effect of pyrite is, however, to initiate deposition, as iron compounds are commonly observed in the innermost slag layer [2]. During combustion, pyrite transforms according to the following scheme:

The iron oxysulfide melt (Fe-S-O) phase of this sequence initiates deposition because of the high deposition efficiency of Fe^{2+} phases such as Fe_{1-x}S and FeO . Subsequently, the Fe-S-O deposit oxidizes to Fe_2O_3 . Therefore, there exists an incentive to study the transient evolution of pyrite as a means of motivating control strategies for fouling and slagging.

1.2 REVIEW OF RELATED WORK

In this section, we will review literature pertinent to the role of pyrite in fouling and slagging in order to determine issues requiring further study. Literature is quite extensive for technological aspects of fouling and slagging but not for high-temperature pyrite kinetics. As a general introduction to the technological incentive for understanding fouling and slagging, Reid's review paper [1] is recommended. It synthesizes the knowledge on coal mineral matter that had been available by 1981. Mineral matter deposition is shown to be the limiting factor on the performance of pulverized coal power stations. This work, however, does not treat certain aspects of the physical and chemical phenomena that lead to fouling and slagging.

The physical and chemical bases of fouling and slagging are more thoroughly covered in a review by Badin [2] three years later. In it, the results of hundreds of studies are presented and can be arranged according to a sequence of issues that leads directly to high-temperature pyrite reactions. The first topic in this sequence is the definition of different types of fouling and slagging deposits. Following this are studies that elucidate sticky alkalinity, those physical and chemical characteristics of mineral matter and furnace walls that lead to the deposition. The three types of chemical reactions that contribute to sticky alkalinity are described, with emphasis on reactions of iron pyrite (FeS_2) derivatives. Also cited are studies that establish that Fe^{2+} phases such as Fe_{1-x}S and FeO are more sticky alkaline than Fe^{3+} phases such as Fe_2O_3 . These studies are confirmed by Abbott and Austin's demonstration [4] that FeS deposits more effectively than Fe_2O_3 , thereby arresting earlier speculations that Fe_2O_3 initiates deposition. Finally, the numerous studies that characterize pyrite transformations at low temperatures (typically under 1000K) are described.

In contrast, few high-temperature kinetics studies are described. These, however, are needed to predict deposition, since such predictions require knowledge of the duration of the melt phases under typical operating conditions. To find the few existing relevant high-temperature studies one has to look elsewhere in literature.

Jorgensen's investigation of the combustion of pure pyrite particles [5] provides a foundation for the study of high-temperature pyrite kinetics. The oxidation of pyrite of various particle size classes (from under-37 microns to 74-105 microns) was monitored at various oxygen levels (from 0% to 21%), furnace wall temperatures (670K to 1170K), and residence times (10 msec to 210 msec). Qualitative X-ray diffraction analysis, Leco

furnace determinations of sulfur, and atomic adsorption spectroscopic measurements of iron established that combustion occurs in three main stages: first, preheating to an invariant ignition temperature of 870K; second, desulfurization until complete conversion to pyrrhotite (Fe_{1-x}S) and particle fragmentation by 970K; finally, formation of an Fe-S-O melt, with rapid escalation of particle temperature to 1750K. In addition, cross-section micrographs of the reacted pyrite revealed that the reaction front forms on the particle surface and penetrates radially inward.

From Jorgensen's studies, the significance of certain operating conditions was demonstrated. Decreasing particle size, increasing oxygen level, and increasing temperature all accelerate the desulfurization kinetics. Moreover, the impact of particle size was shown to increase with decreasing oxygen level by studies performed at 970K and 100 msec.

Asaki [6] generalized these observations to suggest that the particle size becomes important in operating domains with low oxidation rates. This was accomplished by monitoring the oxidation of pyrrhotite ($\text{Fe}_{0.97}\text{S}$) of two particle sizes (nominally 51 and 88 microns) at various furnace temperatures (697K to 1015K) and oxygen levels (5% to 30%) at 1.8 sec residence time. Qualitative X-ray diffraction analysis established that the pyrrhotite is converted to Fe_3O_4 and negligible amounts of Fe_2O_3 . Gravimetric measurements were used to determine the extent of this conversion. Below 825K, the smaller-sized pyrite achieves a significantly higher pyrrhotite conversion than the larger. Above 923K, the oxygen level minimizes the significance of both wall temperature and particle size.

Huffman and Huggins [7] indirectly extended the list of important operating conditions to include the carbon associated with pyrite in coal. Associated carbon apparently retards pyrite oxidation. Huffman and Huggins oxidized pyrite enriched coals (particle size of 38-45 microns and 45-74 microns) at high gas temperatures (1311K to 1727K) at 5% oxygen for residence times ranging from 0.1 to 1.25 sec. Mossbauer spectroscopic analysis of these particles revealed that after oxidation at 1311K in 5% O_2 for 170 msec, the iron phase partition still includes 15% FeS_2 and 33.6% Fe_{1-x}S . But Jorgensen's earlier observation of 72% desulfurization at 970K in 5% O_2 at 100 msec residence time [5] implies that Huffman and Huggins's pyrite should have demonstrated substantially greater conversion (furthermore, unlike Jorgensen's pyrite, these pyrite exhibit a uniform dispersion of oxide and sulfide phases after reacting).

Recently, Srinivasachar and Boni [3] have synthesized the effects of most of the

significant operating conditions into a model for the combustion of pure pyrite particles. In this model, pyrite combustion is treated as analogous to coal combustion, consisting of pyrolysis and oxidation. FeS_2 pyrolyzes to $\text{Fe}_{0.877}\text{S}$, then oxidizes exothermically to Fe-S-O and later to Fe_3O_4 . If the oxygen level is high enough and the temperature is low enough, the Fe_3O_4 continues to oxidize to form Fe_2O_3 .

The pyrite combustion model achieves its technological importance because, ultimately, the duration of the melt phase is the question to be addressed by pyrite kinetics studies. With the model, the melt phase's duration is calculated to be approximately proportional to the square of the particle diameter and inversely proportional to the oxygen level. In addition, increasing gas temperature is shown to decrease the duration of the melt phase. Moreover, associated carbon is taken to increase the melt phase's duration. Consequently, pyrite-induced fouling and slagging can be qualitatively predicted on the basis of pyrite particle size, associated carbon, oxygen level, and temperature.

1.3 UNRESOLVED ISSUES

Quantitatively, Srinivasachar and Boni's pyrite combustion model is limited by the studies from which it is derived. The first major limitation consists of the ambiguities introduced by the studies' feed materials. Pyrite coagulates even more strongly than coal, and this obscures the experimental results. First, coagulation degrades attempts at particle size classification during dry-sieving, as demonstrated by Hoonstra [8]. Second, unsteady feeding leads to dramatic fluctuations in particle number density and temperature [5]. Third, interparticle interactions during combustion invalidate the isolated particle model.

In addition to pyrite coagulation in the parent studies, the incorporation of Huffman and Huggins's Fe_3O_4 oxidation rate may also introduce inaccuracies in the pyrite combustion model. Huffman and Huggins's studies [7] were performed with carbonaceous feed materials and their quantitative results may not apply to pure pyrite particles.

Determining the impact of carbon requires separate studies using tightly-sized pyrite particles uniformly distributed in uniformly-sized carbon particles having a uniform pore structure. Unfortunately, such particles have not yet been reported. Senior [9] has, however, described a procedure for synthesizing porous carbons with silica inclusions, and Levendis and Flagan [10] have modified it to synthesize spherical carbon particles of uniform size. Perhaps, with additional modifications, Senior's procedure could be used to synthesize arbitrarily uniform pyrite-loaded carbon particles.

Like the feed materials, the drop tube studies' diagnostics also introduce ambiguities in the combustion model. Current diagnostics neither distinguish SO from SO₂ nor quantitatively resolve the condensed iron phases. The pyrite combustion model is based on the assumption that SO is the gas phase oxidation product without direct evidence. Some authors, however, assume it is SO₂ (perhaps from thermodynamics) [6], while others assume it is SO, based on temperature predictions of models with adjustable parameters [11]. In contrast, Mossbauer spectroscopy, used by Huffman and Huggins [7, 12], is widely accepted as a means of resolving condensed iron phases. Nevertheless, even Mossbauer spectroscopy's accuracy is guaranteed only for FeS₂-FeS mixtures.

As an alternative to Mossbauer, Pike [13] presents X-ray diffraction analysis (XRD). XRD is a well-developed technique that can resolve the common iron phases [14,15]. Pike's application of XRD to analyze coal ash is, however, undermined by his procedure and the presence of carbon in his samples. Therefore, the need remains for diagnostics capable of resolving the kinetics of pyrite combustion.

Consequently, this literature survey suggests several issues in high-temperature pyrite kinetics that merit emphasis. The first is good materials: non-coagulating pyrite of tight size class as well as size-classified pyrite inclusions in size-classified carbonaceous particles of uniform pore structure. The second is quantitative diagnostic techniques for gas and condensed phase products of the combustion of both pure pyrite particles and pyrite inclusions in a carbon matrix. When these issues have been resolved, kinetics constraints on pyrite combustion may be inferred from comparisons with thermodynamics predictions.

1.4 SCOPE OF PRESENT STUDY

The objective of the present work is to introduce an experimental program that will eventually lead to time-resolved iron ash compositions over the technological operating domain. The preceding literature survey suggests two important stipulations on any such experimental program. The first stipulation is that good control must be established over the operating conditions, to accurately quantify their effects. The other is that data must be obtained rapidly, to thoroughly cover the important operating domain.

Such an experimental program must account for the various forms of pyrite: pure excluded particle, core within a carbon shell, as well as inclusions in a carbon matrix. It must also account for variations in the macroporosity of the carbon matrix. Consequently, the effects of not only operating conditions such as oxygen level, temperature, and char particle diameter would be quantified, but those of pyrite particle size and associated carbon as well.

This work presents a series of studies that has characterized the desulfurization of pyrite during the early stages of combustion. An experimental system was established and used to monitor the effects of oxygen, temperature, and residence time on the evolution of condensed phase products of the combustion of pure pyrite.

The first component of our experimental system consists of techniques for the rapid production of uniform pyrite feeds. These pyrite feeds are uniform in their particle size as well as spatial distribution. The first type of feed comprises tightly size classified extraneous pyrite, specially treated to eliminate coagulation during feeding. The other type of feed consists of pyrite inclusions embedded in a synthetic carbon matrix. The pyrite particle size, its spatial distribution, the carbon's pore size, as well as the pores' spatial distribution all supersede present standards of uniformity. Although the production rate of these materials is only a few grams a day, our production method is still significantly faster than comparable techniques.

The combustion of these pyrite feeds is achieved in the radiant suspension flow reactor [16,17,18], primarily because of its low feed requirement. The reactor has been modified to allow for oxygenated flows as well as longer residence times. In the reactor, particulates are entrained in a one-dimensional laminar gas flow and radiatively heated for residence times of several hundred milliseconds. At the reactor exit, the combustion products are quenched and separated according to aerodynamic size, with the condensed phases being collected on filters. By varying the oxygen level, furnace wall temperature,

and residence time (gas bulk flow rate), we have prepared samples to analyze changes in the composition of the condensed phases.

Analyzing these samples has, however, required our development of the intrinsic standard method of X-ray diffraction (XRD) analysis. XRD was suggested by Pike's study [13], primarily because of its low sample requirement and rapid analysis time. We, however, withhold the internal standard, and instead make our analysis quantitative by using the intrinsic standard method.

With these three components of our experimental system in place, we have been able to monitor the first few hundred milliseconds of pyrite combustion. Comparisons with thermodynamics calculations indicate that the observed pyrite desulfurization corresponds to what is expected at a temperature of several hundred degrees below the furnace wall temperature.

When analyzing these results, one should bear in mind that this research is limited to the most pertinent aspects of pyrite combustion. Only the condensed phases have been monitored because they contribute more to fouling and slagging than the vapor phase. Furthermore, since the oxy-sulfide melt phase initiates fouling and slagging, we have focussed on the early stages of combustion.

CHAPTER 2

MATERIALS

2.1 INTRODUCTION

Iron-ash evolution can be properly characterized only when the initial composition and size distribution of the mineral impurities are known. The proposed research therefore utilizes synthetic materials with monodisperse pyrite constituents and a range of controlled pore structures, including the mesosphere structures common to p. f. firing. Studies with these synthetic materials establish an essential reference condition for analyzing the behavior of coal. The compositions of ash particulates from the synthetic materials will be monitored during simulated p.f. firing.

Synthetic materials for the pyrite thermochemistry experiments can be segregated into two main types. The first of the required samples are raw pyrite particles having a median size greater than 20 microns, to study the thermochemistry of extraneous pyrite under simulated p. f. firing conditions. The second class of samples are synthetic chars loaded with pyrite inclusions smaller than 5 microns, to study the impact of carbon on the pyrite thermochemistry, and to assess the impact of intra-particle diffusional resistances during oxidation. Synthesis, classification, and characterization procedures were developed and implemented to produce substantial amounts of both classes of samples.

An expedient materials preparation scheme is essential to our program, because so many factors affect iron ash evolution. The first group of these factors comprises the material's characteristics, including pyrite particle size, pyrite loading, the proportion of carbon, number, sizes, and connectedness of the macropores, and the oxidation reactivity of the carbon. The second group of factors consists of the operating conditions: gas temperature, oxygen level, residence time, particle size, and suspension loading. Characterizing these influences in a series of flow reactor experiments will obviously require substantial amounts of sample. When mineralogical analysis is required, at least 20 mg of iron ash must be recovered from every run to perform X-ray diffraction

analysis; therefore, we can expect that at least 200 mg of char will be consumed in every run. In total, several grams of each type of synthetic char are required.

Moreover, the samples must be homogeneous, because iron ash evolution may strongly depend on several aspects of the char's physical structure. It is especially important to control the initial size distribution of the pyrite, because it directly factors into the transport resistance. We would also like to independently characterize the effects of variable pyrite loadings and char macroporosities. Surely, substantial fractions of the synthesized char will be discarded during the ultimate classifications into samples with nearly uniform pyrite loading and macroporosity, so tens of grams of each char type will have to be prepared.

This chapter describes the preparation scheme for pyrite, as well as carbonaceous materials. As explained in the following sections, various methods for tightly classifying the raw pyrite inclusions were investigated, leading ultimately to a segregation scheme based on sedimentation which is fast and quite effective. To prepare materials for our extraneous pyrite studies, wet sieving was also utilized in addition to sedimentation, for it proved effective at eliminating oversized particles. The inclusions were used in a carbon synthesis procedure based on Senior and Flagan's [9].

2.2 PYRITE INCLUSIONS

2.2.1 Introduction

The pyrite inclusions for our studies was prepared from -200 mesh stock of regular grade pyrite (at least 90-92% purity) obtained from American Minerals Company. In our thermochemistry studies, the need to control the pyrite particle size stems from concerns related to char quality, experimental method, as well as theoretical interpretation of results. The intraparticle diffusional resistance increases with the square of particle diameter. Also, pyrite inclusions larger than five microns settle quickly enough during the synthesis to result in non-uniform pyrite loading. Moreover, because the collection elements for our flow reactor are quartz filters, the pyrite particles must be larger than the filter's nominal pore size (99.99% collection efficiency for 0.3 micron aerosol).

Two methods to prepare pyrite inclusions were evaluated, wet sieving and sedimentation. The tightness of the size distributions as well as the rate of preparation was emphasized. In each case, pyrite coagulation degrades the size distribution, by causing the retention of fines. We had to devise a means of overcoming this problem before size classifying the pyrite.

Consequently, the following procedure was adopted for preparing our pyrite inclusions. The pyrite is pulverized in a hydraulic press to inhibit coagulation. Afterwards, it is size-classified for 2-to-5 microns, using the sedimentation procedure.

2.2.2 Size Classification of Pyrite by Wet Sieving

Two classification schemes were evaluated for the pyrite inclusions. The first is a wet sieving technique developed by Prof. Self and coworkers for his DOE program on the radiative properties of flyash. The wetsiever is an apparatus that establishes an oscillating water flow through a stack of sieves; while the net flow is in the downward direction, the upward pulsations minimize clogging of the filters. The wetsiever was run with 4, 8, and 16 micron sieves, each of 3-in diameter and 1-in height. Each sieve was filled with water and 5 ml of Coulter Clenz. The Coulter Clenz is a low viscosity soap that inhibits particle agglomeration. Because of sieve blockage, this system can process only 80 mg of ground pyrite per run. The pyrite was dispersed into solution with ultrasound for several minutes, then poured onto the top sieve (16 micron). Water was added continuously as the top sieve dried out, and the wetsiever was run for 45 minutes. Much of the pyrite passed through the bottom sieve (4 micron), and the remainder was equally distributed among the 4, 8, and 16 micron sieves.

The performance of the wet sieving system is unsuitable. Size distributions are described in Sec. 2.2.4 and compared to those from the second classification scheme. Although the system works well for particles larger than ten microns, with our pyrite samples, the sieves clogged very rapidly, thereby retaining many fines in the larger stages. Microscopic examinations of the sieves revealed that clogging was caused by agglomerated fines, rather than by large, individual particles. Agglomeration thereby significantly reduces the amount of sample that may be processed per run, and makes wet sieving a very slow, ineffective method.

2.2.3 Size Classification of Pyrite by Sedimentation

To overcome the problems associated with wet sieving, we developed a system to classify the inclusions on the basis of sedimentation times. The theoretical basis is the well-understood problem of a spherical Stokesian particle undergoing free fall in a quiescent fluid. For such a particle, the differential equation of motion is:

$$m \frac{d^2 x}{dt^2} = m_{\text{net}} g - 3\pi\mu d \frac{dx}{dt} - \frac{\pi}{12} \rho d^3 \frac{d^2 x}{dt^2},$$

$$x(0) = 0$$

$$\frac{dx}{dt}(0) = 0$$

where

m = particle mass,

x = depth,

t = time,

m_{net} = particle mass - displaced fluid's mass,

g = acceleration of gravity,

μ = dynamic viscosity,

d = particle diameter,

and

ρ = density of fluid,

The solution to this equation is:

$$x = \frac{\alpha m_{\text{net}} g}{\beta^2} \left(e^{(-\beta t/\alpha)} - 1 + \frac{\beta t}{\alpha} \right),$$

where $\alpha = m + \pi \rho d^3/12$

and $\beta = 3\pi\mu d$

The terminal velocity is obtained by setting the acceleration to nil in the differential equation above; it is proportional to $\rho_{\text{net}}d^2g/\mu$, where ρ_{net} is the difference between the particle and fluid densities. For pyrite (s.g. of 5) in water (s.g. of 1 and viscosity of 0.89 centipoise), the terminal velocity is reached in much less than a second for the particle sizes of interest, while sedimentation velocities are of the order of a cm/min. Consequently, the acceleration stage is inconsequential.

Terminal velocities of pyrite in water are listed in Table 2.1 for particle diameters from 1 to 50 microns. The broad range of velocities for the sizes of interest constitutes the basis of a practical size segregation technique.

Table 2.1 Calculated Settling Velocity of Pyrite in Water

Diameter (μm)	Velocity (cm/min)
0	0.0
5	0.4
10	1.5
15	3.3
20	5.9
25	9.2
30	13.2
35	18.0
40	23.5
45	29.7
50	36.7

Using the sedimentation velocities in Table 2.1, we developed a procedure for obtaining size-classified pyrite inclusions:

- I. To pretreat pyrite stock before size classification,
 1. Obtain the sub-38 micron class of pyrite that has been classified with a mechanical shaker.
 2. Pulverize 1g of pyrite at a time in a 1-inch diameter mortar using a hydraulic press. Apply 15 tons of force twice, with stirring in-between.

II. To eliminate oversized particles,

- 3. In each of two 2L beakers, place 30g of pyrite.**
- 4. To each beaker, add 25ml of Coulter Clenz and enough water to form 400ml suspension. Shake the beakers vigorously for about 1 minute to mix the suspension thoroughly.**
- 5. Place the beakers in an ultrasonic bath, and let the pyrite particles settle. By ultrasonication, agglomeration is inhibited as the particles settle. The duration of settling is calculated from the sedimentation velocity for the upper cutoff size as well as the distance from the top to the bottom of the suspensions.**
- 6. Decant the liquid. Save the decanted liquid in a storage vessel because it contains those particles that are smaller than the stipulated upper cutoff size.**
- 7. Repeat steps 4 to 6 using the settled remains from the preceding cycle seven more times.**
- 8. After particles settle in the storage vessel, decant the aqueous phase.**

III. To remove undersized particles,

- 9. Divide the particles in the storage vessel evenly between two 2L beakers.**
- 10. To each beaker, add 25ml of Coulter Clenz and enough water to form a 400ml suspension. Shake the beakers vigorously for about 1 minute to mix the suspensions thoroughly.**
- 11. Place the beakers in an ultrasonic bath, and let the pyrite particles settle. The duration of settling is the calculated sedimentation time for a particle of the lower cutoff size to settle from the top to the bottom of the suspensions.**
- 12. Decant the liquid. Discard it, since it contains only (but not all of) the undersized particles.**
- 13. Repeat steps 10 to 12 seven more times using the settled pyrite.**
- 14. Decant and boil off the water from the suspensions remaining in the beakers to recover the pyrite.**

Preliminary studies with the sedimentation technique established three results: (1) the sedimentation procedure is reproducible; (2) the vertical mixing induced by ultrasonication does not degrade the size segregation; (3) the sedimentation procedure is more effective than wet sieving. The size measurements used to establish these facts were taken with a Coulter Multisizer and are reported in the next section.

2.2.4 Measured Size Distributions of Inclusions

The Coulter Multisizer measures the electrical resistance of a saline solution as a particle passes through a calibrated orifice. Then the volume of the cylindrical particle that would yield the same resistance is assigned and attributed to the measured particle. Finally, the volume is converted to the diameter of a sphere having the specified volume. In the distributions reported below, it is especially important to note that only particle sizes between 2% and 60% of the orifice diameter are recorded, and various orifices have been used in these studies.

The size distribution of the ground, unclassified pyrite appears in Fig. 2.1. This size distribution, like all others in this section, is the mass-weighted cumulative distribution. Note that this measurement was taken with a 100 micron orifice, so that the amount of particles smaller than 2 microns is unknown. Nevertheless, the upper end of the distribution is represented fully, and we see that about 80% of the sample is larger than the maximum target size of 5 microns.

The efficiency of the sedimentation scheme for removing the larger particles is evident in the distributions in Fig. 2.2; note that these measurements used the 30 micron orifice, so that sizes larger than 0.6 microns were recorded. In these cases, the sedimentation time was set to eliminate all sizes larger than 4 microns. This study was performed while the sedimentation procedure was still evolving; the suspension contained only 5g of pyrite, the lower cutoff size was attacked before the upper cutoff size, and eleven rounds of settling were used when attacking the upper cutoff size. Roughly 82% of the sample is, in fact, smaller than 4 microns, while less than 5% is larger than 10 microns. The duplicate measurement seen in Fig. 2.2 confirms that the procedure is reproducible.

Figure 2.1 Mass-based cumulative distribution of pyrite obtained from American Minerals, after grinding, but before size classification.

Figure 2.2 The mass-based cumulative distributions from two attempts to recover pyrite inclusions under 4 microns from the raw grind using sedimentation. Reproducibility is evident in the replicate distributions.

The influence of ultrasound was studied with a pyrite sample which contained no particles smaller than about 3 microns. Ultrasonication was applied and withheld during sedimentation experiments aimed at eliminating all particles larger than 9 microns; in both cases, the suspension was sonicated prior to sedimentation. The two distributions in Fig. 2.3 for these cases confirm that ultrasonication while settling does not significantly alter the size distribution of the classified material.

Figure 2.3 Comparison of sedimentation scheme for size classification that ultrasonicates particles as they are settling (solid curve) with one that ultrasonicates particles before they settle (dotted curve).

A comparison between the distributions prepared with wet sieving and sedimentation appears in Fig. 2.4. The size distribution of the residue collected on the 4 micron screen after wet sieving is shown as the dotted line, along with that for classification with sedimentation into the range of 4 to 8 microns. Sedimentation is clearly more effective at removing the fines; in this case the target cutoff size is actually achieved. But the sieved sample has almost one-half its mass below 4 microns. And even though the nominal range of openings in the sieve is tighter than the range in the

sedimentation case, sedimentation also yields a comparable cutoff at the upper end. With sedimentation, 3, 6, 71, 77, and 82% of the mass is below 3, 4, 8, 9, and 10 microns, respectively. With the sample recovered from the 4-6 micron sieve in the wet siever, 21, 48, 86, 88, and 88% were under 3, 4, 8, 9, and 10 microns, respectively.

Figure 2.4 Comparison of effectiveness of two size classification schemes: sedimentation (solid curve) and wetsieving (dotted curve). Plotted are mass-based cumulative distributions from attempts to obtain particles in the range of 4 to 8 microns.

Sedimentation is especially advantageous with regard to the amount of the raw, ground pyrite which is recovered in the desired size range. With sedimentation, 10% of the raw sample (10 g) is in the desired fraction, of which 30% is larger than 8 microns. The yield from wet sieving is almost two orders of magnitude lower, and not classified as well. The wet siever processes only 80 mg of raw pyrite in 45 minutes. Based on the recovered amounts in the desired size range, and the 40 minutes needed to clean sieves between runs, we estimate that the production rate is much lower than 20 mg/hr of classified pyrite. In contrast, with sedimentation, 1 g of classified pyrite can be prepared in 4 hours, at a rate of about 0.25 g/hr.

2.2.5 Parametric Study of Sedimentation Procedure

As the sedimentation procedure was evolving, we introduced the following minor changes to arrive at the ultimate preparation procedure in Sec. 2.2.3. The number of successive sedimentations was reduced from 11 to 8, when classifying for the upper cutoff size. We also discovered that tighter size distributions are obtained by attacking the upper size cutoff before attacking the lower size cutoff. The distribution is tightened even further by increasing the concentration of pyrite in the suspension during the sedimentations. Each of these modifications will be discussed briefly.

Beforehand, it should be recognized that the size distribution of classified pyrite is improved by grinding the raw stock. Unground raw stock subjected to sedimentation yields a broad size distribution with a median size above 5 microns when classified for 2 to 5 microns. We performed studies to assess the effects of grinding by using the sub-38 micron size class of -200 mesh pyrite that had been classified with a mechanical shaker. This stock is evaluated against a batch which was crushed twice at 15 tons before applying the sedimentation procedure. Both samples were sedimented 8 times to remove the particles below 2 microns then 8 more times to recover particles smaller than 5 microns.

The size distributions of both samples appear in Fig. 2.5. Both batches have negligible weight fractions under 2 microns. And although both distributions contain substantial amounts above 5 microns, crushing before sedimentation does lead to reductions in the upper cutoff size. For the crushed sample, the median size is 4.0 microns, and about 60% is smaller than 5 microns.

During the actual sedimentation stage, formerly, the fines were removed by sedimentation before the inclusions smaller than the upper cutoff were recovered. But typically up to half of the material classified by sedimentation was over the desired cutoff of 5 microns. This suggested that the particles were falling slower than the calculated sedimentation velocity. We hypothesized that by attacking the upper cutoff with the fines present, the settling velocities might be accelerated by the drag fields of neighboring particles. The size distributions in Fig. 2.6 with opposite cutoff sequences confirm this hypothesis. Attacking the upper cutoff first increases the amount of particles below 5 microns from 58 to 66%, and only negligibly increases the amount below 2 microns from 2.4 to 2.6 %.

Figure 2.5 Comparison of size distributions of 2 to 5 micron pyrite obtained by sedimentation with (solid curve) and without (dotted curve) pregrinding.

Figure 2.6 Comparison of size distributions of 2 to 5 micron pyrite obtained by sedimentation when the upper cutoff is addressed first (dashed curve) and when it is addressed last (solid curve). The initial distribution is represented by the dotted curve.

But if attacking the upper cutoff first yields a tighter distribution because more particles are present, so should increasing the original amount of pyrite in the suspension. This would also enable us to increase the yield of classified pyrite. To establish if this is so, we classified suspensions of 5, 10, 15, 20, and 30g of pyrite in 400 ml of liquid. It should be noted that the two densest suspensions were decanted 11 times, instead of 8. As seen in Fig. 2.7, the size distributions become tighter as the amount of pyrite in suspension is increased, and the upper cutoff size is also lowered. Over the range of sample size from 5 to 30 g, the weight fraction below 5 microns increases from 67 to 80%.

Figure 2.7 Size distributions showing that the quality of 2 to 5 micron class obtained by sedimentation improves as the concentration of pyrite in the suspension increases. Also indicated are the number of times the suspensions were decanted to obtain the upper cutoff.

2.2.6 Pyrite Inclusions for Production Chars

The pyrite was prepared from -200 mesh stock of regular grade (at least 90-92% purity) obtained from American Minerals Company. Two to five micron size-classified pyrite inclusions for the synthetic char were prepared with the sedimentation procedure.

The upper cutoff size was specified to reflect observations concerning sedimentation of the inclusions during the synthesis step. A cross-section micrograph at 1000X was taken of a char sample that had been size classified and also density classified by centrifugation; it was from the density class having the most sample, which was designated as the mode batch. The micrograph showed that only pyrite inclusions smaller than 5 microns are found in the most abundant class of char. Larger pyrite particles are apparently lost from this batch by settling during synthesis and curing. Such settling implies that the observed pyrite loading will be less than the target value if the initial pyrite stock includes material which is larger than 5 microns. So, to ensure that the size distribution and the pyrite loading in the mode batch is the same as what we would calculate at the time of synthesis, we specified the sedimentation times to yield the upper cutoff at 5 microns.

Various batches of pyrite were mixed together as the sedimentation procedure was evolving. Each batch was classified into the 2 to 5 micron range, with at least 67 wt% smaller than 5 microns. The final size distribution is shown in Fig. 2.8 in the mass-based cumulative form, from the Coulter Multisizer. The median size is 3.7 microns, with 2.8% undersize, and 75% smaller than 5.0 microns. The tightness of the size distribution and its median size of 4 microns are well-suited to quantitative mineral analysis.

Figure 2.8 Mass-based cumulative size distribution of pyrite inclusions for production chars.

2.3 EXTRANEOUS PYRITE

2.3.1 Introduction

Our extraneous pyrite is prepared from 60/200 mesh premium grade pyrite (American Minerals). The sizes of the pyrite samples for our raw pyrite studies have to meet two stipulations. To study intraparticle diffusional resistances, the median particle size must be at least 5 to 10 times the size of pyrite particles used as inclusions in our synthetic char. Since the median size of these inclusions is between 3.5 and 4 microns, the target median size of the raw pyrite particles is between 20 and 45 microns. As a second stipulation, the size distribution about this median must be as tight as possible, to minimize variations in transient temperatures in the flow reactor experiments.

Regarding the preparation of large pyrite particles, we had to overcome pyrite's strong tendency to coagulate, which leads to unacceptably broad size distributions. The size distribution in Fig. 2.9 illustrates just how important the issue of particle coagulation is for pyrite. It displays the size distribution of pyrite distributed by Alfa Chemicals as - 100 mesh (below 150 microns). The median size is actually 3.7 microns, with all of the particles being below 6.6 microns. We found that the RoTap, a conventional apparatus for size classifying dry particulates, is unsatisfactory for particles of relatively low conductivity such as pyrite. Furthermore, the coagulation problem is particularly severe when size classification is attempted under dry conditions. In the various conventional schemes evaluated and described in the following sections, coagulation degrades the size distribution.

To overcome coagulation of the fines, we developed a two stage size classification technique preceded by pregrinding. After a sample of 60/200 mesh pyrite stock is ground, to remove fines, the sedimentation procedure is used with the nominal settling time of a 35 micron particle. The remaining pyrite is then wet sieved by hand on a 45 micron screen to attack the upper size cutoff. This procedure yields a median size of 20 microns, as measured by the Coulter Counter.

Figure 2.9 Mass-based cumulative size distribution of -100 mesh (-150 microns) pyrite obtained from Alfa Chemicals. Note that the particles are an order of magnitude smaller than the advertised size.

2.3.2 Size Classification of Pyrite by Dry Sieving

Since the size distribution of raw pyrite stock is so broad, we performed a classification to remove much of the pyrite that fell outside the desired size range of -325 mesh (38 microns)+400 mesh (45 microns). In performing the rough classification our main objective was to remove the fines which tend to coagulate with larger particles.

We evaluated both the RoTap and the sieve shaker and determined that the sieve shaker is more efficient at removing particles smaller than 38 microns. For these studies, we used -325 mesh (-45 microns) American Minerals regular grade pyrite. An amount of pyrite corresponding to 0.26 g/cm^2 was RoTapped on a -325 mesh sieve for thirty minutes. The pyrite recovered on a -400 mesh sieve was Rotapped again through the -325 mesh sieve (at 0.03 g/cm^2 of screen) for thirty minutes. Then the material recovered on the -400 mesh sieve was classified for thirty minutes on the sieve shaker. Between each classification, size distributions of the -325+400 mesh pyrite were determined.

The size distributions appear in Fig. 2.10. There is not much change from the first round of RoTapping to the second round, for which the amount of sub-38 micron particles is reduced only from 77 to 66%. During RoTapping the distributions reach their steady states within thirty minutes. Static charges on the screens seem to retain the fines, and cause clogging. The particle size distribution is significantly improved, however, after a round of sieve shaking, in so far as the percentage of fines is reduced to 50%.

Figure 2.10 Comparison of effectiveness of RoTap (solid and dotted curves) and sieve shaker (dashed curve) for obtaining 38-to-45 micron size class of pyrite. These are mass-based size distributions of the samples showing incremental changes induced by each round of classification.

Next, the influences of pyrite sample size and duration of sieving were examined. In these studies, a fresh sample of -200 mesh (-75 microns) pyrite was used in each run, and the sieve shaker was fitted with 3-in diameter sieves of the following screen openings: 75, 63, 53, 45, and 38 microns. The amount of pyrite was varied from 2.6 to 10g, and the duration of sieving was varied from 30 minutes to 2 hours.

The size distributions for the 38-45 micron size grade for various sieving conditions appear in Fig. 2.11. Note that the size distribution for a sieving time of 2 hours with about 3 g of sample is the only one which is different. Perhaps surprisingly, classification is independent of the amount of pyrite to 10 g of sample. It appears that distributions for sieve shaking reach a steady state within 30 minutes for pyrite loadings as high as 10g. Most important, none of the distributions are adequate for our studies, since about three fourths of the samples are finer than the desired cutoff of 38 microns.

Figure 2.11 Effect of sieving time and initial pyrite loading on the quality of the size distribution of pyrite in sieve shaker's 38-to-45 micron size class. Neither sieving time nor pyrite loading affects the size distribution.

2.3.3 Double-Staged Size Classification: Dry Sieving-Wet Sieving

Dry size classification was ineffective at removing fines. Therefore, we investigated the efficiency of double-staged classification. We decided to perform our preliminary classification by sieving 10g of pyrite on the sieve shaker for 30 minutes.

To eliminate the fines remaining after preliminary classification, the -325+400 mesh pyrite is wet sieved by hand. Five grams of pyrite is mixed with 375 ml of water

and 25 ml of Coulter Clenz soap. This suspension is ultrasonicated for several minutes and poured onto a 1-in high 38 micron sieve. While on the sieve, the pyrite is washed for about two minutes. After each washing the sieve is cleaned by ultrasonication. After washing, only 27% of the initial amount of pyrite is still on the sieve.

As seen in Fig. 2.12, wet sieving substantially eliminates fines, but only for fines smaller than about 10 microns. This classification also increases the median size from 20 microns to 24 microns. While still very broad, the ultimate size distributions are significantly tighter than after dry size classification.

Figure 2.12 Effectiveness of wet-sieving (dashed curve) on the size distribution of pre-classified pyrite (solid curve). The pyrite was washed on a 38 micron screen after it was extracted from the sieve shaker's 38-to-45 micron class.

2.3.4 Size Classification of Production Extraneous Pyrite: Sedimentation-Wet Sieving

The pyrite used in this study was prepared from 60/200 mesh premium grade pyrite (American Minerals). Impurities are present at less than 2 wt% and consist primarily of quartz. Ten grams of our samples were first pulverized twice in a mortar and pestle under 15 tons in a hydraulic press. Fines were eliminated by sedimentation in water with

a surfactant in an ultrasonic bath, using the nominal settling time for a 35 micron particle as the cutoff time. The suspension consisted of 30g of pyrite, 25 ml Coulter Clenz, and 375 ml of water. Eight repetitions were performed with each batch. Finally the remaining sample was wet-sieved by hand through a 45-micron sieve.

The cumulative mass distribution of the sample, determined with a Coulter Counter, appears in Fig. 2.13. The median size is 20 microns, with a standard deviation of 5 microns. In contrast, for a sample prepared with sieving through 38-45 micron screens on a RoTap for 30 minutes, the median size is actually only 21 microns with a standard deviation of about 15 to 20 microns, and the distribution is asymmetric. About three-fourths of the material is actually smaller than the lower cutoff size of the screen.

Figure 2.13 Mass-based cumulative size distribution of production extraneous pyrite (solid curve) compared with that obtained using the RoTap (dotted curve).

2.4 CHAR SYNTHESIS PROCEDURE

2.4.1 Introduction

The mechanisms of iron ash evolution during p. f. combustion can be elucidated only when the initial composition, size distribution of the mineral inclusions, and pore size distribution of the char are fully characterized. Each of these three quantities is very difficult to characterize for whole coals, so we have undertaken the synthesis of carbons with controlled porosity and pyrite loadings as a central element of this program.

Various schemes for carbon synthesis have been developed over the past few decades. We adopted that of Senior and Flagan at Caltech [9], which is a modification of Walker's synthesis process. Furfuryl alcohol is processed as the monomer in a catalyzed polymerization, using p-toluenesulfonic acid (PTSA). After decanting the aqueous phase, a viscous polymer is cured at progressively higher temperatures, to convert it into a glassy carbon. The detailed procedure is explained in Sec. 2.4.2.

These carbons are especially suitable for our purposes in that they contain no macropores; in fact, Senior reported that no pores larger than 15 Angstroms are present. We add inclusions to control the evolution of macroporosity, particularly those to form voids of several microns, to create the mesosphere structures so often seen in the chars from p.f. firing. Closely sized pyrite particles are also added, at prescribed loadings.

2.4.2 General Description

Synthetic chars in the form of billets of glassy carbon can be produced through the furfuryl alcohol polymerization process perfected by Senior [9]. Senior's char polymerization was repeated and modified by adding pyrite mineral inclusions and lycopodium pore formers. Following are the steps for synthesis:

A: Polymerization

Step 1: Combine 30-40 ml of furfuryl alcohol monomer with the catalyst, p-toluenesulfonic acid (PTSA), in a 200 or 250 ml boiling flask. The catalyst is added in a water solution, 0.0451 g/ml, and is always 0.5% by weight of monomer.

Step 2: Fit the flask with a water-cooled condenser and set in a water bath at 70-73 C for 10 minutes with constant stirring. Note that the amber colored liquid will turn dark brown as water is evolved violently. Finally a distinct aqueous phase will appear.

Step 3: Pour the contents of the flask into a 125 ml separatory funnel and leave for one to one and a half hours.

Step 4: Weigh a 150 ml beaker. Drain the viscous, dark brown polymer from the separatory funnel into the beaker, and discard the aqueous phase. Cover the beaker and weigh again. The amount of polymer is therefore determined.

B: Addition of Solids

At this point, two paths can be followed depending on whether or not lycopodium is to be added.

I. Omitting lycopodium - start with 40 ml of furfuryl alcohol and 5.0333 ml of PTSA solution.

Step 5: Add 0.11 ml of acetone per gram of polymer to the contents of the 150 ml beaker, cover, and place in an ultrasonic bath.

Step 6: Weigh the pyrite (7.9% of polymer weight, when aiming for 10% loading) and add it to the beaker while in the bath.

Step 7: Mix the solution for 15 minutes using an overhead stirrer at 2000 rpm (the desired result can be obtained with a stirring rate as low as 1000 rpm). Note the formation of acetone bubbles.

Step 8: Pour the resulting mixture into four ceramic boats of dimensions 100mm x 20mm x 13 mm (manufactured by Coors Porcelain).

II. Adding lycopodium - start with 30 ml of furfuryl alcohol monomer and 3.775 ml of PTSA solution.

Step 5: Add 0.4 ml acetone per gram polymer to the contents of the 150 ml beaker, cover, and place in an ultrasonic bath.

Step 6: Weigh and add the pyrite (6.44% of polymer weight when aiming for 10% loading) and lycopodium (18.8% of polymer weight when aiming for 50% nominal porosity) separately.

Step 7: Mix the contents of the beaker using the overhead stirrer for 20 minutes at 1000-2000 rpm.

Step 8: Pour the resulting solution into the ceramic boats.

C: Curing

Step 9: Place boats in vacuum oven, and purge with argon for 25 minutes, under approximately 26 inches Hg pressure.

Step 10: Heat the oven to 125 C at approximately 2 C/minute. At 100 C, the polymer will start frothing as water boils off violently. By 125 C, the boiling has stopped, and the polymer has solidified, retaining the bubbles. Hold at 125 C for 6 hours.

Step 11: Heat the oven to 200 C at approximately 1 C/minute. Hold at 200 C for 10 hours.

Step 12: Place boats in atmospheric pressure furnace and increase the temperature of the furnace at a rate of 4-5 C/minute till the soak temperature is reached. The assumed soak temperature for lycopodium is 550 C. Hold at this temperature for 1 hour. At this curing step, the oxygen level should be below a few hundred parts per million to avoid oxidation. Note that by the end of this step the pyrite has been converted to pyrrhotite.

Step 13: Cool the boats in flowing argon. The char produced is in the form of puffy glassy carbon with centimeter-size bubbles.

D: Grinding & Storage

Step 14: Grind the char down to the desired size and sieve for thirty minutes using a mechanical shaker.

Step 15: Store the sample in a dessicator.

2.5 GLASSY CARBON

In our first attempts at synthesis, we were surprised to observe very large bubbles in the carbon samples, which clearly indicated that the melts were foaming during one of the curing stages. Although portions of the carbons were smooth and glassy, like obsidian, larger regions contained centimeter-size voids. We perturbed the synthesis procedure in various ways to attempt to control viscosity and foaming during the curing stage, but saw only marginal improvements. Fortunately, the very large scale porosity is eliminated during grinding and classification into the p. f. size grade.

The SEM micrographs in Fig. 2.14 confirm that this is the case. As seen in the high resolution (1440 power) image of a single particle, no large voids are present, and all surfaces are smooth and glassy. In Senior's samples, there were no pores larger than 15 Angstroms.

Although the carbons prepared by Senior's procedure are suitable for our studies once they are ground, we also tried to modify the synthesis procedure to eliminate foaming. The remainder of this section summarizes these attempts, but only briefly because they were only marginally successful.

In the synthesis, water is the medium for introducing the PTSA catalyst, and even after decanting the aqueous phase, the viscous polymer contains substantial amounts of it. It is removed during four hours of dessication used during these attempts at synthesis, followed by curing at 125 C for 6 hours. Subsequent curing, at 200 C for 10 hours and at 550 C for one hour, expels unreacted monomers and small fragments, and noncondensable gases. Before dessication, the melts must be thinned with acetone so solids can be added. The acetone is driven off by the first curing stage. Even though we were not adding solids at this time, acetone was included to characterize its evaporation.

The melts begin to foam during the first curing stage, at roughly 100 C, and retain the vapor bubbles as the condensed phase solidifies after prolonged curing at 125 C. By modifying the synthesis procedure, to evaporate the water at 90 C under reduced pressure, while the melt is still fluid, then raising the temperature to 125 C, we hoped to eliminate the foaming.

(a)

(b)

1250X

Figure 2.14 (A) SEM micrograph at 1440X of an individual, 100 micron carbon particle synthesized from furfuryl alcohol. (B) Cross-section micrograph at 1250X of synthetic carbon ground into the pulverized fuel grade, without any size classification.

Aside from this modification, the other deviations from the Senior's procedure are thought to be inconsequential. The curing stages are conducted under argon instead of nitrogen. We use a hand-drill fit with a propeller for stirring at up to 1000 rpm, instead of 2000 rpm. Since the complete procedure is given in Sec. 2.4.2, only the curing stages are discussed further.

Since the onset of foaming occurred slightly below the boiling point of water, we tried to eliminate it by progressively reducing the amounts of water and acetone (boiling point of 70C) in the polymer/acetone mixture before the first curing stage. By reducing the pressure during the dessication step, more of the acetone and water could be evaporated before the first curing step. The weight loss from a series of samples at different dessication pressures appear in Tab. 2.2, along with the cumulative weight loss from the three distinct curing stages. These samples represent a wide range of acetone and water contents. Note that samples C1, C2, D1, D2, and F did not contain acetone. Furthermore, sample F contains no water, since the PTSA was added in crystalline form. Samples A, B1, C1, and D1 were dessicated under sub-atmospheric pressure, and lost more mass, as expected.

Table 2.2 Weight Loss of Polymer/Acetone at Various Stages of Char Synthesis*

Sample	Dessication**	125C	200C*	550C*
A	9.6	19.5	—	—
B1	8.4	—	28.4	—
B2	6.6	—	30.5	—
C1†	2.2	—	15.2	—
C2†	1.1	—	15.2	—
D1†	2.3	10.4	—	—
D2†	0.6	9.6	—	—
E	11.7	—	—	43.3
F†	-0.5	—	—	43.1
G	10.3	—	15.8	36.2

*Weight loss in weight percent of original polymer/acetone mixture.

**For samples A, B2, C2, D2, E, F, and G, pressure in dessicator was between 25 and 30 in Hg, and for the rest, it was less than 10 in Hg.

*Values are cumulative for the preceding curing stage(s) only, without weight loss during dessication.

†No acetone was mixed with polymer.

Despite these variations in volatiles content, the foaming was not completely eliminated in any sample. In fact, the foaming was about the same for all samples, with one exception. Only in sample F, which contained no water, was the foaming almost eliminated. We concluded that the dessication pressure and acetone content of the polymer cannot be manipulated to eliminate foaming. Adding the PTSA as crystals is also unsatisfactory, because it is only slightly soluble in alcohol and will likely remain as inclusions in the carbon samples.

2.6 MACROPOROUS CHAR

2.6.1 Introduction

The carbons are uniformly microporous and are suitable only as the medium for adding controlled macroporosity and pyrite inclusions at prescribed loadings. The group at Caltech has identified various pore forming agents to introduce macropores which are continuously distributed in sizes as large as 0.01 to 0.1 micron [9].

Although such materials would be suitable for our studies of pyrite thermochemistry, we would prefer to eliminate the pore size distribution altogether and work with a truly bimodal pore structure. Actually, the micropores are unimportant. At typical p. f. firing conditions, the penetration of oxygen is governed by the macropore structure. But the question remains: what is a suitable characteristic size for the macropores in coal char from p. f. firing conditions?

The most common char structures from high temperature combustion are much more porous than any of the synthetic macroporous materials generated to date. They typically include voids of several microns in size and are categorized as either mesospheres or cenospheres. Mesospheres include tens of macrovoids per particle and have a structure which resembles puff pastry. Cenospheres have structures which are even more open and contain only a few distinct chambers within a thin outer shell. In both cases, the void size is roughly comparable to the particle diameter, being at least several microns.

We decided to devise a scheme to synthesize carbons with the mesosphere structure, in which the macrovoids are spherical with a uniform size and can be introduced at prescribed number densities. The remainder of this section discusses our synthesis procedures and illustrates the structures of the resulting carbons.

2.6.2 Introducing Macrovoids into Synthetic Carbons

For our studies, we would like to introduce macrovoids of at least 10 microns into the glassy carbons. Our approach relies on adding inert inclusions of the proper size which can be vaporized during the curing stages of the carbon synthesis, and meets three constraints: (1) the inclusion size should be uniform; (2) the pore forming agent must vaporize completely during the curing stage of the synthesis and leave no inorganic residue; (3) the number density of voids should be easy to control. Chemical pore forming agents or inert inclusions such as carbon black generate macroporosity on much smaller length scales, and with a broad size distribution. A survey of the thermophysical properties of various inorganic salts yields several candidate materials, although the toxicity of their vapors, their generally good solubility in acetone, and the potential for inorganic residues are problematic.

Lycopodium powder, a type of plant spore, however, satisfies all criteria. It is harvested for aerosol and biochemical research and can be obtained commercially, although we gratefully acknowledge the assistance of Dr. Tangirala of the University of California at San Diego in providing samples.

Lycopodium is a hollow, waxy hydrocarbon spore which is produced naturally in a very narrow size range. The mass-based cumulative size distribution of our samples, determined with a Coulter Counter, appears in Fig. 2.15. Note the minimal dispersion about the mean size of 28 microns. The volatility of the powder was determined by heating it in an oven. At a heating rate between 3 C/min and 5 C/min, the cumulative loss was 93% by 387 C and 97% by 507 C. Consequently, we could expect nearly complete devolatilization during the final curing stage of the carbon synthesis, at 550 C.

Figure 2.15 Mass-based cumulative size distribution of lycopodium powder.

The spores are easily introduced into the polymer melt after the polymerization step, and rather homogeneous dispersions could be obtained with only minor deviations from Senior's procedure for carbon black additions. Without explicit regard for the amount of polymer present, Senior recommended 70 ml of acetone be used when adding pore-forming inclusions, but this level thinned the melt too much for lycopodium. The spores settled to the bottom of the synthesis vessels. We found, however, that an acetone addition of only 2.7 ml per gr of polymer yields well-dispersed samples. The spores were mixed into the melts using an overhead stirrer fitted with a drill and operating at 1000 rpm.

The melts are cured first at 125 C for 6 hours, then 200C for 10 hours, and ultimately at 600 C for 1 hr. The crosssection micrograph in Fig. 2.16 demonstrates the resulting structure of the carbons. This image was obtained from a 100 micron carbon particle imbedded in epoxy and polished to expose an internal section of the particle; the magnification in the photograph is 1250X. Note that the macrovoids appear as dark, circular regions. They are fairly uniform in size, as expected from the uniform size of the spores, but somewhat smaller than the original inclusions. In this particular cross-section, their diameter is about 16 microns, versus 28 microns for the spores. Their

spatial distribution is uniform. In this case, roughly, the area of the voids is forty percent of the total cross section, which is low for the fifty percent porosity expected for this particular synthesis. Finally, note that the epoxy has penetrated all but one void (in the center), and that the voids are connected to the external surface, presumably via rather large fissures opened as the spores are vaporized.

Figure 2.16 Cross-section micrograph at 1250X of a 100-micron synthetic carbon particle with 16-micron pores.

Even when the lycopodium powder settles during the synthesis, the spatial distribution of pores is still uniform. This is because any settled spores will form a tightly packed layer at the bottom of the curing vessels which devolatilizes during curing, leaving very large bubbles, on the order of millimeters. Since these settling-induced voids are of a much larger scale than the pulverized char particles, they do not affect the spatial uniformity of the resulting char pore structure.

Lycopodium is an ideal macrovoid former which meets all design specifications for our studies. It seems to have only one drawback. There are bound to be interparticle variations in the voidage after the bulk samples are ground into the pulverized fuel grade.

Since the bulk particle density is sensitive to the number density of macrovoids, one would hope to segregate particles on the basis of large scale porosity using a range of liquids with small variations in specific gravity in a centrifuge. However, since the voids are often connected to the external surface, they are also penetrated by the liquids, so the macroporous carbons may show the same bulk density as the original glassy carbons. Nevertheless, microscopic examination will later show that interparticle variations are not substantial.

2.7 NON-POROUS PYRITE-LOADED CHAR

2.7.1 Introduction

Carbons which contain pyrite inclusions are needed for the pyrite thermochemistry studies. The locally reducing environment of the carbon particle is expected to alter the chemistry of iron ash evolution during combustion. Furthermore, since the macroporosity of the carbon matrix influences the depth of oxygen penetration, a non-porous carbon is needed as reference for subsequently establishing the thermochemical impact of pore structure.

2.7.2 Introducing Pyrite Inclusions into the Carbons

The micrographs in Fig. 2.17 illustrate the consequences of including large inclusions in the synthesis. The cross section micrographs were taken at a magnification of 500X; the inclusions appear as the white grains (note that by the end of the synthesis procedure, the pyrite inclusions convert to pyrrhotite. Nevertheless, for simplicity's sake we will refer to them as pyrite particles, when not dealing with issues of chemical composition). The chars in Figs. 2.17a and 2.17b were recovered from the top and bottom of the curing vessel, respectively. Pyrite particles smaller than 10 microns are distributed between and within the two groups. Larger sizes, however, are much more concentrated in the samples from the bottom, due to settling. Clearly, the inclusion size must be kept below 10 microns to approach uniform dispersion.

(A)

(B)

Figure 2.17 (A) Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions, from top of synthesis vessels.
 (B) Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions, from bottom of synthesis vessels.

In addition to reducing the diameter of pyrite inclusions, we modify Senior's synthesis procedure to inhibit settling. Senior recommended 0.33 ml acetone per gram of polymer for carbons with silica inclusions, while we find that one-third that level should be used with pyrite. Also, we eliminate the dessication stage that precedes curing.

Although reducing the inclusion size and increasing the viscosity of the polymer improves the dispersion of pyrite throughout the carbons, the pyrite loadings are, in fact, not uniform throughout the carbon samples. Consequently, the samples are subjected to a final classification stage based on bulk density. Liquids of tightly controlled specific gravity are prepared from mixtures of percut (a.k.a. naptha varsol; s.g. of 0.755) with perchloroethylene (s. g. of 1.620). The specific gravity of the solutions is controlled to within 0.02 units. Dispersions of the carbons are then centrifuged at 2500 rpm. The frequency distributions of the carbon samples are determined based on the float and sink classification. Ashing analysis and cross section micrographs are used to monitor the ultimate pyrite loadings in these samples; the loadings are controlled to within 2 wt% absolute.

2.8 MACROPOROUS PYRITE-LOADED CHAR

A procedure to introduce both macrovoids and pyrite inclusions into the carbons was also evaluated. For the case of a pyrite loading of 10 percent and a macrovoidage of 40 percent, the melt is thinned with 0.4 ml acetone per gram of polymer. After their grinding into the p. f. size grade and dry sieving, the samples were classified further by float and sink.

Methods based on density classification were used to control the interparticle variations in both pyrite loading and the proportion of closed macrovoids. This scheme is effective for most types of chars to be used in the laboratory combustion studies. However, due to penetration of the macrovoids, the float and sink classification cannot segregate on the basis of the number density of macrovoids. Fortunately, by examining these samples for uniform macroporosity using the cross section micrographs, one establishes that the number density of pores is already uniform before density classification. Nevertheless, attempts to obtain batches of char with both uniform pore structure and pyrite loading were only partly successful, because the proportion of closed pores is not uniform.

2.9 CENTRIFUGATION PROCEDURE

2.9.1 Motivation

Interparticle variations in the pyrite loading can obscure the interpretations of our experimental results, by affecting the conversion rates. This is because the chemical conversion rate depends on the specific surface area, not the total mass of the pyrite. Suppose there are four pyrite particles concentrated in one of two char particles rather than being evenly distributed between the two char particles. Further suppose that there is no fragmentation and that the pyrite particles of each char just agglomerate. The total chemical conversion that occurs after agglomeration will be less than what would occur if the pyrite had been uniformly distributed, because the specific surface area decreases with increasing particle size.

The difficulties in controlling the pyrite loading during the char synthesis are due to settling during the polymerization stage. Char is synthesized by mixing pyrite inclusions into a furfuryl alcohol resin thinned with acetone. During the mixing process, the resin is also ultrasonicated to achieve short range mixing. If the resin is thin, the ultrasonicator provides good short range mixing (leading to intra-particle uniformity), but the particle settling that occurs leads to poor long-range mixing (resulting in poor inter-particle uniformity). But if the resin is thick, the short range mixing is poor and long range mixing is good. The settling problem can also be controlled by keeping the inclusion size much below ten microns. Nevertheless, because the char sizes of interest are so small, eliminating inhomogeneities during char synthesis is inherently limited. The char has to be classified for uniform pyrite loading after it is produced.

It is important to have uniform distribution of macrovoids in the char samples with high porosity. As for the pyrite inclusions, uniform voidage can be achieved, in principle, by a classification scheme after the char has been cured and ground into the p. f. grade. But another factor comes into play in this subsequent classification. Not all of the voids are interconnected, or connected via pores to the external surface. The proportion of closed porosity may conceivably affect the fragmentation and oxidation rates of the samples, and it certainly complicates the final classification. Even though the voids appear to be uniformly dispersed among the particles, there is no way to homogenize the connectedness of the pore structure by modifying steps in the synthesis process. Here again, a post-synthesis classification scheme is necessary.

2.9.2 Density Classification Based on Centrifugation

To eliminate the inhomogeneities in pyrite loading and pore-connectedness in the synthetic chars, we developed a simple ultracentrifugation procedure to segregate the samples on the basis of their specific gravity. Both pyrite inclusions and macrovoids substantially alter the char density, since pyrite is much heavier than char and the voids have no mass. The method relies upon sedimentation in various liquids which have tightly controlled specific gravity; the centrifugation simply accelerates the sedimentation of the suspension. Consequently, the accuracy of the density classification is governed by control of the specific gravity of the solvent liquids.

For samples which include pyrite but no macrovoids, the bulk density of the particles is directly related to the pyrite loading. In contrast, for chars with macrovoids but no pyrite, since the liquid penetrates through most, but not all, of the macrovoids, ultracentrifugation classifies on the basis of the proportions of closed porosity.

The theory behind ultracentrifugation is the same as that of sedimentation, outlined in Sec. 2.2.3. The only difference here is that the particles that are capable of settling are induced to settle at a much faster rate than they would under gravity. To estimate the amount of time required for particles to settle, one substitutes the centrifugal acceleration at the center of the centrifuge tube for gravity. The relevant parameters for our system are a centrifugation speed of 2500 rpm, radial position of the upper and lower fluid levels of 4.5in and 7.75in, respectively, and fluid viscosity of about 0.89 centipoise. Under such conditions, a 33 micron particle with s. g. of only 0.001 greater than that of the fluid would sink to the bottom of the centrifuge tube within two minutes.

Our centrifugation solvents are binary mixtures of percut (s. g. of 0.755) and perchloroethylene (s. g. of 1.620). The accuracy of our procedure is limited by the accuracy of controlling the specific gravity of the solvent. Moreover, the uncertainty in the liquid's density, ρ , is determined by the uncertainty associated with reading a graduated cylinder, dV , where dV is half the distance between the smallest graduations, and is expressed as:

$$\rho \pm d\rho = \frac{\rho_1(V_1 \pm dV_1) + \rho_2(V_2 \pm dV_2)}{V_1 + V_2 \pm (dV_1 + dV_2)}$$

$$\text{or } \rho \pm d\rho = \frac{\rho_1 V_1 + \rho_2 V_2}{V_1 + V_2} \pm \frac{p_1}{p_2},$$

$$\text{with } p_1 = \frac{s_1 + s_2 \rho}{\rho_2 V_2 - s_2},$$

$$p_2 = \frac{s_1 + s_2 \rho}{\rho_2 V_2 + s_2},$$

$$s_1 = \rho_1 dV_1 + \rho_2 dV_2,$$

$$\text{and } s_2 = dV_1 + dV_2$$

where ρ = specific gravity of the solvent mixture

V_1, V_2 = volume of fluid 1 and 2

and dV_1, dV_2 = uncertainty in measuring V_1 and V_2 .

The amounts of each liquid needed to obtain 40 ml of solution with a specified density appear in Table 2.3, along with the uncertainties in the target densities. In all cases, the uncertainty is less than 0.02 s.g.

Table 2.3 Specific Gravity of Solutions of Percut in Perchloroethylene

Solution S.G	Vpercut (ml)	Vperchloroethylene (ml)	S.G. Error
0.76	39.8	0.2	0.01
0.80	37.9	2.1	0.01
0.84	36.1	3.9	0.01
0.88	34.2	5.8	0.01
0.92	32.4	7.6	0.01
0.96	30.5	9.5	0.01
1.00	28.7	11.3	0.01
1.04	26.8	13.2	0.01
1.08	25.0	15.0	0.01
1.12	23.1	16.9	0.01
1.16	21.3	18.7	0.01
1.20	19.4	20.6	0.02
1.24	17.6	22.4	0.02
1.28	15.7	24.3	0.02
1.32	13.9	26.1	0.02
1.36	12.0	28.0	0.02
1.40	10.2	29.8	0.02
1.44	8.3	31.7	0.02
1.48	6.5	33.5	0.02
1.52	4.6	35.4	0.02
1.56	2.8	37.2	0.02
1.60	0.9	39.1	0.02

The detailed procedure for our density classification scheme is:

I Char preparation

1. Grind char and sieve it to a size greater than 30 microns.

2. Dry the char as well as some analytical filter paper in a vacuum oven for 4 hours at 120C under a pressure of less than 1 in Hg.

3. Weigh and store both the char and the filter paper in a dessicator until you are ready to begin centrifugation.

II Centrifugation

4. Add 1g of char to each centrifuge tube.

5. Mix percut and perchloroethylene to a selected solvent density. Table 2.3 shows how much of each fluid to mix in order to get 40 ml of solvent for various specific gravities.

6. Add 20 ml of the specific gravity liquid to each centrifuge tube and stir with a spatula.

7. Centrifuge for 2 min at 2500 rpm.

8. Decant onto a piece of filter paper within a funnel which is attached to a suction device. While decanting, notice the transition from particle-laden suspension to clear liquid. Stop when the clear liquid reverts to suspension. All particles less dense than the centrifuge liquid are now on the filter paper.

9. When the filter paper dries, put it aside. Place a new filter paper on the funnel.

10. Repeat steps 5 to 9 with progressively heavier specific gravity liquid until finished.

III Post-centrifugation processing of char

11. Dry the filter papers, which now contain char, in a vacuum oven for 4 hours at 120C under a pressure of less than 1 in Hg.

12. Remove the filter papers from the oven, and let cool in a dessicator for 5 min.

13. Weigh the char if necessary.

Results are reported in the next two sections.

2.9.3 Density Classification to Control the Pyrite Loading

This section includes results for density-classified synthetic chars with pyrite inclusions; no macrovoids were introduced. The relation between char density and pyrite loading is obtained by dividing the mass of the constituents of a char particle by its

volume. The organic carbonaceous portion of the aggregate is denoted by the term "char matrix". The relation is:

$$\rho = \frac{\rho_p \rho_c}{y_p \rho_c + (1 - y_p) \rho_p}$$

where

ρ = density,

y = mass fraction,

and subscripts p and c denote pyrite and char matrix, respectively.

In Table 2.4, values of density calculated from this expression are tabulated as a function of the density of the char matrix and mass fraction of pyrite. For specific gravities from 1.1 to 1.36, the tabulated density range, the pyrite mass fraction is approximately defined as the aggregate char density minus the density of the char matrix.

Table 2.4 Char Specific Gravity for Various Pyrite Loadings and Densities of the Char Matrix

Char Matrix S.G.	Pyrite Loading (wt%)						
	4	6	8	10	12	14	16
1.10	1.14	1.15	1.17	1.19	1.21	1.23	1.26
1.12	1.16	1.17	1.19	1.21	1.24	1.26	1.28
1.14	1.18	1.20	1.22	1.24	1.26	1.28	1.30
1.16	1.20	1.22	1.24	1.26	1.28	1.30	1.32
1.18	1.22	1.24	1.26	1.28	1.30	1.32	1.34
1.20	1.24	1.26	1.28	1.30	1.32	1.34	1.37
1.22	1.26	1.28	1.30	1.32	1.34	1.36	1.39
1.24	1.28	1.30	1.32	1.34	1.36	1.39	1.41
1.26	1.30	1.32	1.34	1.36	1.38	1.41	1.43
1.28	1.32	1.34	1.36	1.38	1.41	1.43	1.45
1.30	1.34	1.36	1.38	1.40	1.43	1.45	1.47
1.32	1.36	1.38	1.40	1.42	1.45	1.47	1.50
1.34	1.38	1.40	1.42	1.45	1.47	1.49	1.52
1.36	1.40	1.42	1.44	1.47	1.49	1.51	1.54

To implement this relation, the density of the char matrix must be specified. It was measured by applying our ultracentrifugation procedure to a pure, non-porous char sample ground to pass through a 175 micron sieve. Both the cumulative and differential density distributions for the pure carbon appear in Fig. 2.18. Note that the differential distribution is evaluated with the density at the midpoint of each density interval. As expected, the density of the pure char is restricted to a narrow range. None of the char has a s. g. below 1.24, and about half the sample has s. g. between 1.26 and 1.28.

Figure 2.18 Cumulative and differential density distributions of the synthetic char matrix. The density distributions were obtained by ultracentrifuging non-porous, mineral free char in solvents with tightly controlled specific gravities.

Similar density distributions for the char with pyrite inclusions appear in Fig. 2.19. The target loading in the synthesis of this material was 10% pyrite; 90% of the inclusions were smaller than 8 microns. Before ultracentrifugation, the char was ground and sieved on a RoTap for 30 minutes to obtain particles in the 90 to 106 microns range. The distributions in Fig. 2.19 are shifted to higher densities, as expected, and the dispersion about the mean is only slightly greater than for the pure char. None of this char has a s. g. below 1.24, as required for consistency with the density of the char matrix. Here also,

about half the sample lies within a very tight density interval, between s. g. of 1.30 and 1.32. The calculated pyrite loading corresponding to this density range is, from Table 2.4, 4 +/- 2%. It is much lower than the target loading, probably, because of settling during synthesis, loss during grinding and size classification, and void creation around inclusions.

Figure 2.19 Cumulative and differential density distributions of non-porous char synthesized to have 10% pyrite loading. The density distributions were obtained by ultracentrifuging in liquids of various specific gravities.

Cross-section micrographs of samples from various density classes show good interparticle dispersion of the inclusions. The 1.26 to 1.28 s.g. class was expected to have no pyrite, since that is the density class of the char matrix, but the 1.30 to 1.32 class was expected to have about 4% pyrite. Micrographs of particles from these two classes appear in Fig. 2.20. As expected, the 1.31 s.g. char has substantially more inclusions than the 1.27 s.g. char, although the lighter char does have inclusions. One possible explanation of this inconsistency is that the addition of pyrite creates closed voids that makes the char lighter than it would be otherwise. We later developed a scheme to recover the ash following combustion of the carbon matrix to independently determine the loading of the density classified chars.

(a)

(b)

Figure 2.20 Cross-section micrograph at 500X of 100-micron synthetic carbon particles with pyrite inclusions.
 (A) Specific gravity of 1.26 to 1.28.
 (B) Specific gravity of 1.30 to 1.32.

2.9.4 Density Classification to Control the Dispersion of Macrovoids

Ultracentrifugation is a means of segregating our char particles according to their proportion of closed voids. Since the voids are introduced as distinct inclusions- the lycopodium spores- the macrovoids are initially unconnected. But during curing, the spores vaporize, and the vapor forms channels between voids and to the particle surface. However, as seen in the micrographs in this section, some of the voids remain isolated, and the closed porosity significantly alters the particle density. After segregating the char by density, we examined its photomicrographs to verify that the density classes correspond to different proportions of closed porosity.

The relationship between char density and closed porosity is straightforward. During ultracentrifugation, the solvent penetrates only the open voids. Consequently, the ratio of the density of the char matrix (i.e. non-porous char) to the density of a porous char is an indicator of the amount of closed pores the porous char contains.

We synthesized char with a target porosity of 75%. The only modifications made to the synthesis procedure reported in Sec. 2.6.2 was to triple the amount of lycopodium added, to 56.4% of the polymer weight. We also reduced the amount of acetone to 0.8ml per gram of polymer.

Fig. 2.21 shows the density distributions of our high porosity char. Before it was ultracentrifuged, the char was sieved by hand for 15 minutes to obtain particles in the 60 to 175 microns range. The density distribution obtained from ultracentrifugation is quite broad and is shifted towards lower values with respect to the char matrix, as a result of the addition of pores. The lightest char particles are of 1.05 s.g., and the densest are, as expected, of 1.28 s.g. (i.e. no closed pores).

Figure 2.21 Cumulative and differential density distributions of mineral-free char synthesized to have 75% porosity. The density distributions were determined by ultracentrifuging char in fluids of controlled specific gravity.

After ultracentrifugation, two density classes were photomicrographed to confirm that their density difference was due to their differing proportions of closed pores. Micrographs of particles having specific gravities in the range 1.16 to 1.18 and also 1.26 to 1.28 appear in Fig. 2.22. In the micrographs, open pores appear within the external boundaries of the particles with the same neutral gray color as the epoxy resin in the background of the micrograph. Closed voids appear in black. Note that the two groups have comparable number of pores, which are well-distributed, but that the denser char has a much lower proportion of closed voids, as expected. Although the proportions of closed porosity cannot be controlled during synthesis, it appears that this variation can be controlled by ultracentrifugation to obtain fairly homogeneous batches of char.

(a)

(b)

Figure 2.22 Cross-section micrograph at 100X of 65-175 micron particles of highly porous synthetic carbon.
 (A) Specific gravity of 1.16 to 1.18.
 (B) Specific gravity of 1.26 to 1.28.

2.9.5 Density Classification to Control Both Pyrite Loading and Macrovoidage

Experiments will also be run with samples which contain both pyrite inclusions and macrovoids. Neither pyrite loading nor the macroporosity can be controlled during synthesis, and the density classification for chars with pyrite and voids by ultracentrifugation is ambiguous. A char particle with a large amount of pyrite and closed pores will have the same density as a char particle with little pyrite and few closed pores. But we also found that the density of the char matrix as well as the density of non-porous pyrite-loaded char is tightly bounded. Since the char matrix has a density of 1.27, the maximum density of porous char is 1.27, if the pyrite is neglected. If the pyrite mixing is as good as in the non-porous case, then a density peak occurring above 1.27 would suggest a homogeneous pyrite loading and few closed pores.

Char, synthesized to have 10% pyrite loading and 50% porosity, was density classified. The char was ground and sieved to obtain particles of 90 to 106 microns then ultracentrifuged. The density distribution obtained by ultracentrifugation appears in Fig. 2.23. Since it extends to much lower values than that of non-porous, pyrite-loaded char, there are substantial proportions of closed porosity in this material. The minimum density is greater than that for the char without pyrite and 75% porosity (in Sec. 2.9.4), as expected. The maximum density, however, is much greater, because of the pyrite inclusions.

Basically, the distribution for porous, pyrite-loaded char resembles the superposition of the distributions of non-porous, pyrite-loaded char and of mineral-free, porous char. As expected, there are two modes: one at 1.27 s.g. and the other at 1.31 s.g..

Cross-section micrographs of char of 1.26-1.28 s.g. and of 1.30-1.32 s.g. appear in Fig. 2.24. Here again, the voids are uniformly dispersed. However, the proportion of closed pores does differ significantly between these two classes and, as expected, this proportion is much lower in the char of greater density.

The pyrite loading seems to follow the same tendency. Substantially more pyrite is seen in the char with higher density, although within both samples there is a noticeable variation of pyrite loading. This variation seems worse for the 1.27 s.g. class.

These results indicate that ultracentrifugation has to be used with care to obtain char with both uniform porosity and pyrite loading. The only class that is reasonably uniform is that corresponding to the expected peak of non-porous pyrite-loaded char, because most of the char in this density class has relatively few closed voids. However,

there is still greater heterogeneity in this class than for either the case of mineral-free char or non-porous char.

Figure 2.23 Cumulative and differential density distributions of char synthesized to have 50% porosity and 10% pyrite loading. The density distributions were obtained by ultracentrifuging char in fluids with controlled specific gravities.

(a)

(b)

Figure 2.24 Cross-section micrograph at 250X of 100-micron particles of highly porous synthetic carbons with pyrite inclusions.
 (A) Specific gravity of 1.26 to 1.28.
 (B) Specific gravity of 1.30 to 1.32.

2.10 CHN-ASHING ANALYSIS

The segregation by density is done on the basis of density intervals as tight as 0.02 specific gravity units. According to calculations, such variations correspond to variations in pyrite loading of 2 wt%. To verify the actual loadings by direct measurements, we, however, devised a scheme based on ashing in our elemental analyzer. The CHN analyzer combusts char at 970C in an oxygen-helium atmosphere and detects product compositions to assign the sample's carbon, hydrogen, and nitrogen content. For our purposes here, only the weight of the residue after complete combustion is relevant.

Of course the weight of the inorganic residue is not equivalent to that of the pyrite in the sample, because during combustion sulfur is expelled and the iron is oxidized. The relation between these amounts was assigned from calibration studies with unfused mixtures of non-porous, unloaded synthetic char and 2-to-8 micron iron pyrite in various proportions.

The calibration curve appears in Fig. 2.25 and is shown as the fractional weight loss based on the initial amount of pyrite versus the pyrite weight fraction in the sample. Clearly, the weight loss is not the same for all mixtures; at 4 wt% pyrite, the loss is 22%, and it rises to 29% for 100 wt% pyrite.

As an illustration, this calibration is implemented in the characterization of a batch of loaded chars with a targeted pyrite loading of 10 wt%. The inclusions were classified so that about 70% were smaller than 5 microns. Because this sample includes so many oversized particles, 12 wt% of pyrite was added during synthesis, to compensate for sedimentation losses. The chars were then ground, sieved, and density classified by centrifugation. The final distribution of specific gravities appears in Fig. 2.26, and both the differential and cumulative distributions are shown. All of the char has an s.g. between 1.24 and 5.0, with a mode in the 1.28 to 1.30 s.g. class. Note especially that the mode comprises 40% of the char sample.

Figure 2.25 Basis for calibration factors for relating amount of pyrite remaining after ashing in the elemental analyzer to initial amount of pyrite in synthetic carbon. Plotted is the fraction of initial pyrite lost during ashing for various values of initial pyrite content of a synthetic carbon/pyrite mixture.

Figure 2.26 Cumulative and differential density distributions of non-porous char synthesized to have an average loading of 12%. The density distributions were obtained by ultracentrifuging char in liquids of various specific gravities.

Pyrite loadings were assigned by each density class. The results appear in Fig. 2.27; data points (and the dashed line) are based on the calibration, while the solid curve is based on values calculated assuming an effective s. g. of the char matrix of 1.20 (which accounts for cracks in the char matrix induced by the addition of pyrite). The error bars reflect the ranges of specific gravity in the intervals in the density classification. While the uncertainties are very large at specific gravities greater than 1.6, we are interested only in the lower density ranges. Most important, the pyrite loading of the mode batch of char is 10 wt%, as intended. Moreover, the measured pyrite loadings correspond to the calculated pyrite loadings in all density classes, within the experimental uncertainty.

Figure 2.27 Comparison of the pyrite loading obtained by CHN-ashing with the values calculated on the basis of char density for the different classes of the sample synthetic char.

2.11 Production Chars

2.11.1 Non-Macroporous Pyrite-Loaded Char

The procedures to prepare synthetic microporous carbons with classified pyrite inclusions involve multiple grindings, size classification, and density classification. Attrition in each step takes its toll and, to rely on the broadest measure of conversion, only 2.85g of the targeted char was recovered from 15.43g of size classified pyrite inclusions. The percentage of the original pyrite inclusions recovered after each stage of char processing appears in Table 2.5. In the stages prior to ultracentrifugation, the pyrite recovery is not measured directly, but equated with the char recovery.

Table 2.5 Fraction of Initial Pyrite Remaining after Various Stages of Char Processing

	<u>Non-Porous Char</u>	<u>Porous Char</u>
<u>Processing Stage</u>		
Grinding	92.30%	95.48%
Regrinding	not applicable	87.00%
Sieving	9.67%	8.13%
Ultracentrifugation	1.50%	1.67%

The processing began with 83.4g of char, including 15.43g of pyrite inclusions, but yielded only 1.50% of the pyrite. Losses during grinding are modest, but size classification seems very wasteful. Only 9.67% of the original pyrite inclusions end up in char of the desired size class, 90-106 microns. Actually, substantial amounts were also

classified into 63-75, 75-90, and 106-125 micron cuts, which may also be used in the experiments.

The final processing step segregates according to pyrite loading with ultracentrifugation with specific gravities (s.g.) of 1.28, 1.30, 1.32, and 1.34. From the density class with the most amount of char, 1.30-1.32 s.g., only 2.85g of char was recovered. This char constitutes our production material. CHN-ashing indicated a pyrite loading of 8.1%, in very good agreement with the targeted value of 8-10%.

The char's size distribution was measured with the Coulter Multisizer using a 280 micron orifice tube. It is shown in Fig. 2.28 in mass-based cumulative form. Its median size is 94 microns, with a standard deviation of about 11 microns. Although 35% and 15% of the char is undersize and oversize, respectively, the distribution is still tight by current standards. The fairly uniform dispersion of the inclusions throughout the carbon matrix is apparent in the cross-section micrograph in Fig. 2.29.

Figure 2.28 Mass-based cumulative size distribution of non-porous production char. The nominal size class is 90 to 106 microns.

Figure 2.29 Cross-section micrograph at 625X of non-porous production char. Shown are 100 micron char particles with 2 to 5 micron pyrite inclusions.

2.11.2 Macroporous Pyrite-Loaded Char

Pyrite-loaded char with macrovoids was prepared, and its recovery was a little lower than its non-porous counterpart's because of the additional classification for closed porosity. Lycopodium spores are added during the polymerization and vaporized during curing. A total of 98.35g of char was synthesized with 14.73g of pyrite. After grinding, sieving, and ultracentrifuging the char to obtain our production materials, only 1.67% of this pyrite was left in the 2.01g of char.

The pyrite losses during each processing stage are in Table 2.5. Two stages of grinding were needed, only because the disk grinder is not a precision instrument. After sieving 2.8g of char at a time for 30 minutes on a sieve-shaker fitted with 63, 75, 90, 106, 125, and 150 micron meshes, we were left with only 8.13% of the synthesized material in the targeted size class.

This small amount of material was further reduced during the last processing step, ultracentrifugation. Using density separation fluids with s.g. of 1.28, 1.30, 1.32, and 1.34 to segregate the char into classes with homogeneous pore structure and pyrite loading, we encountered a problem. The density class containing the most char had only 1.69g of material, too little for the projected reactor experiments. However, the pyrite loadings of some of the density classes, based on CHN-ashing, are finely graduated. The classes of 1.30-1.32 s.g. and 1.32-1.34 s.g. have pyrite loadings of 12.1% and 12.6%, respectively. Combining the two density classes gave us 2.01g of production materials with 12.2% pyrite loading, or merely 1.67% of the original pyrite inclusions.

Like its non-porous counterpart, the porous production char was analyzed for size and spatial dispersion; its porosity is also easy to estimate. The size distribution appears in Fig. 2.30. Its median of 90 microns is slightly smaller than that of the non-porous char in Fig. 2.28, and the distribution is broader, with a standard deviation of at least 13 microns. The dispersion of the inclusions in the porous char is just as uniform as in the non-porous sample. As seen in Fig. 2.31, both the inclusions and the macrovoids are distributed fairly uniformly.

Figure 2.30 Mass-based cumulative size distribution of porous production char. The nominal size class is 90 to 106 microns.

Figure 2.31 Cross-section micrograph at 625X of macroporous production char. Shown are 100 micron char particles with 28 micron pores and 2 to 5 micron pyrite inclusions.

The photomicrographs also enable quantitative estimates of the porosity. In the image, the visible pores necessarily intersect the plane of the cross-section, and their centers must lie within plus-or-minus one pore radius of the plane. Therefore, the visible pores are centered in a slab as thick as the pore diameter over the cross-section of the char, suggesting that the porosity can be estimated as

$$\frac{\pi n d^3}{6 A d},$$

where n = number of pores,
 d = pore diameter (28 μm),
 and A = char cross-section,

Applying this formula to the nine char particles in Fig. 2.32 (taken at 250X) yields a mean porosity of 38% and a standard deviation of 6.8%.

Figure 2.32 Cross-section micrograph at 250X of macroporous production char. Shown are 100 micron char particles with 28 micron pores and 2 to 5 micron pyrite inclusions.

CHAPTER 3

RADIANT SUSPENSION FLOW REACTOR

3.1 INTRODUCTION

This chapter describes a reactor suitable for determining the kinetics of pyrite transformations. According to Srinivasachar and Boni [3], pyrite combustion consists of pyrolysis and oxidation, and we seek to isolate and characterize each stage. To achieve this, we must parametrically vary the reactor's operating conditions. A wide range of temperatures, oxygen levels, and residence times must be traversed with accuracy, resolution and speed.

Distinguishing pyrolysis from oxidation is best achieved in a reactor capable of operating both with and without oxygen. The general parameters of pyrolysis are elucidated by operating without oxygen. Then the impact of gas phase oxidation on pyrolysis can be established by adding oxygen and operating at low temperature and short residence time. By subsequently increasing the oxygen level, temperature, and residence time, the solid phase oxidation stage can be characterized.

If the gas phase reactions are also to be characterized, independent control of gas and particle temperatures must be attained. Determining the primary reaction products stipulates gas temperatures low enough to prevent secondary reactions. This is often not achievable in convective flow reactors and requires a novel approach.

To study a wide range of operating conditions, a reactor with a low minimum feed requirement is needed, since our production rate of materials is so low. On the other hand, the reactor's maximum feed requirement must be at least several hundred milligrams per operating condition to be compatible with solid phase diagnostics requirements. Moreover, obtaining meaningful data from each operating condition imposes several additional restrictions on the reactor. First, the fuel particles should experience uniform conditions. Furthermore, representative sampling is best attained by

collecting the entire combustion product. Finally, the reactor's operation should be always stable and reproducible.

3.2 REACTOR DESCRIPTION

3.2.1 Overview

The radiant suspension flow reactor was selected for our experiments, primarily on the basis of its low feed requirement. It is also particularly suitable for future studies of gas phase reactions, as it can provide a cool gas environment that minimizes secondary reactions.

A schematic of the suspension flow reactor appears in Fig. 3.1. The reactor's prototype is fully described elsewhere [16,17], although for our experiments a version with a longer furnace section is used [18]. At the top of the system, a feeder delivers fuel particles into an argon entrainment stream, forming an optically-thin suspension which flows downward into a radiant furnace section. Near-blackbody thermal emission from the graphite walls rapidly heats the particles as they traverse the furnace. Time resolution is achieved by varying the gas transit time from the furnace inlet to an argon quench nozzle mounted near the outlet of the radiant section. Upon quenching, the reaction products are segregated into particulates, aerosol, and noncondensable gases using virtual impaction in an aerodynamic classifier. Each of these aspects of the reactor is described in more detail in the following sections.

3.2.2 The Particle Feeder

The suspension flow reactor's feeder circumvents two problems usually observed with fluidized bed feeders. The particle feedrate and gas flowrate are not dependent. In addition, the size distribution of the feed does not change with time.

Figure 3.1 The radiant suspension flow reactor.

In Fig. 3.2 is shown a schematic of the feeder. The feed material is placed inside a brass tube and forced to its top by a teflon rod. From the lip of the brass tube, the particles are scraped by a wedge onto a ramp leading into a 40 cm long copper flow tube. The particulates are dispersed as they are transported down the copper tube. Several centimeters above the furnace entrance, the copper tube is joined to a quartz tube. With this feeder, coal feedrates from 0.2 to 7g/min can be maintained.

Figure 3.2 The particle feeder.

The particle suspension enters a 20 mm I. D. quartz tube from the 10 mm copper tube, and is stabilized on the centerline by a co-flowing, argon sheath flow. The relative flowrates of the entrainment and sheath flows are set to minimize the extent of particle dispersion over the length of the furnace. They are not matched; rather, the conditions which yielded a uniform, pencil-like flow of coal (not pyrite) over the furnace length at each gas velocity in cold-flow visualization studies are implemented in the experiments. Also, the suspension loadings are based on the cross section of only the entrainment stream and the calibrated fuel feedrate.

3.2.3 The Inductively-Heated Radiant Furnace

The radiant section consists of a quartz tube situated on the axis of an inductively-heated graphite cylinder. Note that the suspension is optically thin because of its small diameter, so that the radiant heat flux is uniform, and no mixing with a preheated gas stream is involved. Also, since the argon is transparent to the radiation, the gas remains relatively cool, thereby minimizing secondary reactions among the volatiles. Although suspension loadings up to several thousand particles per cubic centimeter are maintained, the behavior in this system can be interpreted in terms of single-particle phenomena because the interparticle separation is at least ten particle diameters.

The design of the furnace section is illustrated in Fig. 3.3. The induction furnace has a 12.5 cm radiant section consisting of a graphite cylinder encased in zirconium oxide insulation which is wrapped by a water-cooled, copper induction coil. This assembly is mounted within water-cooled copper plates and a pyrex housing. In the prototype reactor, the overall height of the furnace is 9.5 cm, although the active length of the hot zone is only 5 cm; the current furnace, however, has a 12.5 cm radiant section. The graphite is heated inductively by a 10 kW, 450 kHz power supply. Wall temperatures are monitored with a disappearing filament pyrometer sighted onto the graphite through a small hole in the insulation to an uncertainty of 20K, and temperatures to 1850K are attainable. In characterization studies of the prototype with two-color pyrometry, axial temperature profiles within the graphite enclosure are uniform to within 98% of the mean temperature, except for the outermost 5 mm at both ends, over which the temperature falls to about 75% of the mean value.

For this system, three approaches are routinely used to assign the residence time. The first, used in Sec. 3.2.5, consists of performing direct measurements under experimental conditions. With this method, residence times are assigned as the time interval between the interruption of two HeNe laser beams by the leading edge of a long pulse of suspension. An alternative approach is to calculate the residence time on the basis of momentum and energy equations (Sec. 3.3). The final method, is to report nominal residence times calculated from the bulk gas flowrate at room temperature (Chap. 5).

Figure 3.3 The inductively-heated radiant furnace.

3.2.4 The Virtual Impactor

At the furnace exit, the flow is quenched by an argon quench nozzle and sent into the virtual impactor. All of the condensed phase products (particulates and aerosol) are recovered. Although the particle feedrate is stable and reproducible, for pure pyrite, their respective yields cannot, however, be assigned gravimetrically due to deposition.

The virtual impactor is shown in Fig. 3.4, and at its inlet, the cooled process stream contains particles, aerosol, and noncondensable gases at low levels in an argon stream. Most of the inlet stream is diverted radially outward into the annulus while a small portion passes through the central nozzle. This split is maintained by valves downstream of the impactor. Particles with sufficient inertia, viz., large particulates, pass through this virtual impaction surface and into a wire mesh basket. Nominal sizes for the aerosol from inorganic ash could be as large as a few microns, while the char particles are on the order of 50 microns, so the separation efficiency is very high. For 50 micron coal particles, the separation efficiency into the mesh basket exceeded 97% in characterization studies, so that carry-over of char into the annulus is negligible.

Figure 3.4 The virtual impactor.

A small portion of the inlet gas stream, typically 5%, passes through the lower nozzle, while the remainder of the flow convects the aerosol products into the annulus, where they deposit onto a glass fiber filter. If the accumulation of aerosol leads to an excessive pressure drop, multiple (up to four) stages of filters are used, and the top stages are punctured to decrease their flow resistance. Most of the aerosol deposits onto these stages, and the final stage scavenges the stream at the size threshold of the filters (0.3 microns).

3.2.5 Reactor Performance in Coal Pyrolysis

An illustration of the performance of the prototype reactor in kinetics studies appears in Fig. 3.5 [16]. This study examines variations in residence time at selected wall temperatures to characterize the kinetics of mass loss and tar evolution during rapid

coal devolatilization. Results appear for wall temperatures of 1570, 1680, and 1840K. Although the wall temperatures are fixed in these studies, particle temperatures are increasing with increasing residence times and never attain the wall temperature in the available furnace length (see Sec. 3.3).

Figure 3.5 Total (OPEN symbols) and aerosol yield (FILLED symbols) for Illinois #6 coal, 75-106 μm , diamond 1840K, inverted triangle 1680K, triangle 1570K wall temperature, 400 particles/cc [16].

The onset of devolatilization shifts to shorter residence times as the wall temperature is increased, as expected. The complete transient evolution is evident only at 1840K, and shows two distinct stages of product evolution delineated by a surge in the evolution rate between 72 and 77 ms. Although they do not convey the entire approach to ultimate yields, the transient yields at 1680 and 1570K reliably convey the onset of devolatilization and the relatively small amount of tar formed during the initial stages. Of course, with the current version of the reactor, greater yields would be observed at each wall temperature, due to the much longer radiant section.

3.3 PARTICLE TEMPERATURES AND PARAMETRIC SENSITIVITY

An integral component of our study of the pyrite transformation is a computer model of the particle temperature history. The model, used in conjunction with experimental results from the radiant suspension flow reactor, will aid in finding kinetic parameters for the transformations as well as calculate the thermal histories of the particles. This pyrite temperature model is a modification of an in-house particle temperature program that was developed by Lau [22] to analyze devolatilization data from the pyrolysis of coal in the radiant suspension flow reactor. This model included the coupled particle and gas energy balances, gas momentum equation, as well as a detailed analysis of the radiation exchange within the furnace. The major assumptions in the model are: (1) particles are spherical; (2) the particles can be treated as a lumped mass with no interparticle heat exchange; and, (3) the gas is isothermal at any given axial location. The predicted coal and gas temperatures as functions of axial position fit expected trends fairly well, but residence times are off by a factor of two from measured values.

Simulations with the original computer model showed that we can independently control the particle and gas temperatures. A coal suspension in a 4 slm flow of nitrogen was simulated with the reactor wall at 1600 K [18]. Since all suspensions of interest are optically-thin, because of their small diameter, the radiant flux is independent of number density. Nevertheless, the particle and gas histories in Fig 3.6 reveal that the suspension loading is a significant factor. It is important to realize that only the suspension loadings differ for these cases (75, 400, and 2400 particles/cm³); gas flowrates, wall temperatures, and particle sizes are the same. For the dilute suspension, the gas is significantly cooler than the suspension, by 100 K at the furnace outlet. In contrast, for the dense suspension, the gas temperature closely tracks the suspension temperature because interphase heat transfer is proportional to interfacial area, and both outlet temperatures increase with increasing suspension loading. Even with the densest suspensions, the wall temperature is, however, never attained in the available residence time.

Experiments run with highly disparate suspension loadings of coal (400 and 3000 particles/cm³) validate the trends in the simulations. Aerosols were separated and recovered from char and dissolved in tetrahydrofuran, to assess sooting. For the dilute suspension, ultimate devolatilization yields are achieved, and the tar is completely soluble. For the dense suspension, the ultimate yield is again achieved, but in less time, and the aerosol is completely insoluble in THF, so that sooting is complete. These results are relevant to pyrite thermochemistry studies in demonstrating that the extent of secondary homogeneous chemistry can be controlled in this system.

Figure 3.6 Calculated particle (solid curves) and gas (dashed curves) temperature histories in the radiant suspension flow reactor for various suspension loadings. The suspension consists of coal in a 4 slm flow of nitrogen at a furnace temperature of 1600K [18].

Gas and particle temperature histories for extraneous pyrite suspensions calculated from the pyrite particle temperature model appear in Fig 3.7. These simulations are performed at the actual experimental condition (from Chap. 6) having the lowest furnace temperature at which pyrolysis is observed, 1260 K. The conditions are for 39000 particles/cm³ of 20 micron pyrite particles in a 3.9 slm flow of argon. The particle emissivity was varied because a value is not reported in the literature. Since pyrite is a non-metal, its emissivity is expected to exceed 0.2; the emissivity of coal provides an upper bound of approximately 0.7.

Fig 3.7 illustrates the effect of pyrite emissivity on the particle and gas temperature histories. For the low emissivity, the gas and particle temperatures are virtually equal; for the high emissivity, the particle temperature reaches an excess of 35 degrees before merging with the gas temperature. More importantly, the heating rate increases with the pyrite's emissivity. Nevertheless, the particle temperature still falls several hundred degrees below the furnace temperature in both cases.

Figure 3.7 Calculated particle (solid curves) and gas (dashed curves) temperature histories in the radiant suspension flow reactor for various emissivities of pyrite. The suspension consists of 39000 particles /cm³ of pyrite in a 3.9 slm flow of argon at a furnace temperature of 1260K.

The pyrite particle temperature model, PYRTEMP, will also be used to assign kinetic rate parameters for the rapid high temperature pyrolysis of pyrite in an inert environment from the transient conversion data. The only reported parameters in the literature are based on data for slow heating conditions in the temperature range 600°C to 650°C [23]. In our study, the activation energy and frequency factor for single first order rate expression will be assigned from transient conversion data, although a distributed activation energy model could easily be implemented if the conversion cannot be explained with the simpler kinetic model.

Of all the uncertainties associated with the particle energy balance, the pyrite emissivity is one of the largest. As mentioned above the emissivity of pyrite has not been reported in the literature. To assess the sensitivity of the kinetic rate parameters to the value of the emissivity, PYRTEMP was used to find those ordered sets of activation energy,

frequency factor, and emissivity which matched the measured yield of 53.3% at a velocity of 50 cm/s. Fig. 3.8 shows the results, plotted as frequency factor versus activation energy for different values of emissivity. Because the curves diverge for larger values of the kinetic rate parameters, the effects of changing emissivity become more pronounced at the higher values of both parameters. A change of 0.5 to 0.9 for the emissivity changes the frequency factor by one order of magnitude for 10^8 sec^{-1} and by two orders for 10^{16} sec^{-1} . For the same change in emissivity, the change in activation energy is approximately 10%. This study shows that an uncertainty of as much as 0.4 in the emissivity results in an uncertainty of 10% in the activation energy.

Fig. 3.8 PYRTEMP calculated ordered pairs of frequency factor and activation energy for various emissivities and the following conditions: $V_{\text{cr}} = 50 \text{ cm/sec}$, feed rate = 0.54 g/min, $T_w = 1626 \text{ K}$ and outlet yield of 53.3%

3.4 OPERATING CONDITIONS FOR OXIDATION STUDIES

The radiant coal flow reactor is too short to study the complete transient evolution of iron ash. The system was really designed for devolatilization studies, with time scales much shorter than typical oxidation times. Notwithstanding, there is a feasible operating mode. The suspension is ignited in the radiant furnace section, then the downstream flow tube is extended to permit further oxidation outside of the furnace until the low effective radiant collection temperature extinguishes the combustion. In this section, the combustion times for various oxygen concentrations are used to specify the tube lengths.

To estimate the amount of tubing needed to attain different degrees of char burnoff, we solved the problem of a spherical carbon particle burning in a laminar pipe flow. The burning is assumed to occur in diffusion-limited mode with CO as the product. In addition, the particle velocity is assumed to be equal to the gas's. In this problem, the particle and gas temperatures as well as the particle burning rate are coupled. The following three equations describe the system:

$$1) \quad q = \frac{2(2MDC) \ln(1 + X_{O_2})}{d_p}$$

$$2) \quad \frac{\rho_p C_p U_p}{a_{sp}} \frac{dT_p}{dz} = - \frac{Nu_p k}{d_p} (T_p - T_g) - \sigma \epsilon_p (T_p^4 - T_w^4) + q \Delta H$$

$$3) \quad \frac{\rho_g C_g U_g \pi d_t^2}{4} \frac{dT_g}{dz} = \frac{n_p \pi d_p^2 Nu_p k (T_p - T_g) \pi d_t^2}{4 d_p} - \frac{Nu_t k (T_g - T_w) \pi d_t}{d_t}$$

- where
- q = particle mass burning rate,
 - M = atomic weight of particle (carbon = 12),
 - D = diffusion coefficient of oxygen in gas,
 - c = gas molar concentration,
 - X_{O_2} = oxygen mole fraction,
 - d_p = particle diameter,

ρ = density,
 C = specific heat at constant pressure,
 a_{sp} = particle specific area ($6/\text{diameter}$),
 T = temperature,
 t = time,
 Nu = Nusselt number ($Nu_p = 2$, $Nu_t = 3.658$),
 k = thermal conductivity of gas,
 σ = Stefan-Boltzman constant ($5.729 \times 10^{-8} \text{ W/m}^2\text{k}^4$),
 ϵ = emissivity,
 ΔH = heat of combustion (C oxidation to CO),
 U = velocity,
 z = axial distance,
 and n = number density,

with subscripts

p = particle,
 g = gas,
 w = wall,
 and t = tube

The first relation defines the diffusion-limited burning rate, including the effect of the mole change (Stefan flow) on the rate. The particle energy equation balances the fuel's thermal capacitance against the convective and radiative losses and the reaction exotherm. The energy equation for the gas phase balances the advection of sensible enthalpy against convection from the suspension and to the tube walls. These equations are integrated numerically with the Euler method using specified increments in axial distance. After each increment, all parameters are updated.

Here we focus on the simulation of 100 micron char fed at the minimum feasible rate (200 mg/min) at the longest residence time in the radiant section. The suspension loading is about 300 particles/cm³. In lieu of a model for the heat-up and ignition stages, the suspension temperature at the outlet of the radiant section is taken at 1550K. The tube wall downstream of the furnace remains at 300K.

The computed char diameters for three oxygen concentrations appear in Fig. 3.9. Even for oxygen levels below 10%, a 25 cm extension tube should provide sufficient residence time. An extension up to 30 cm can be easily accommodated.

Figure 3.9 Calculated char diameter in O₂-Ar flow through a quartz tube added to the exit of the radiant furnace. At the inlet, the suspension temperature is 1550K; the tube wall remains at 300K.

CHAPTER 4

X-RAY DIFFRACTION ANALYSIS

4.1 INTRODUCTION

Following the combustion experiments, the compositions of the solid residues must be determined. Two broad stipulations are placed on our chemical analysis. First, quantitative detection of the expected major phases must be resolved to concentrations of about 5 wt%. In addition, rapid analysis of a large number of samples must be feasible.

Based largely on equilibrium product compositions, the major expected phases are Fe_{1-x}S and Fe_3O_4 as well as FeS_2 , Fe_{1-x}O and Fe_2O_3 to a lesser extent [7]. Given the number of important species, identifying only the elemental distribution is not adequate for kinetics studies. Consequently, conventional analytical techniques such as gravimetry, titration, Leco furnace determinations, and electron microprobe analysis are not sufficient.

Mossbauer spectroscopy, however, achieves the desired analysis [7]. For FeS_2 - Fe_{1-x}S systems, Mossbauer spectroscopy is quite effective [12]. Unfortunately, the oxides usually make the resolution of Mossbauer spectra difficult. Nonetheless, the determining limitations against Mossbauer spectroscopy are actually placed by the second stipulation on our chemical analysis, rapid analysis of a large number of samples. Due to the limited amounts of feed materials, only about 20 mg of iron ash species would be available from each operating condition (for synthetic carbons). Mossbauer, however, requires about double that amount, thereby halving the number of monitorable operating conditions. Moreover, each analysis is 24 hours in duration.

A more expedient scheme is suggested by Pike et al. in X-ray diffraction analysis (XRD) [13]. Previous drop tube studies with pyrite utilized XRD to achieve accurate phase identification in conjunction with quantitative determinations of elemental composition [5,6]. Some even use it as a semi-quantitative scheme [20]. Pike et al. went

further, by attempting to quantitatively resolve the proportions of illite, kaolinite, quartz, gypsum, pyrite, and ankerite in low temperature ash. Their effort was met with mixed results, however.

Generally, quantitative XRD is easily utilized with only certain types of materials. Glassy and amorphous phases possess broad peaks that deteriorate diffraction pattern resolution, thereby diminishing the utility of XRD in the analysis of whole coals. Interference from the carbon matrix also constitutes an impediment with whole coals. In extraneous pyrite studies, however, these problems are averted, for the quenching of melt phases is not believed to be fast enough to yield amorphous products.

4.2 AN OVERVIEW OF X-RAY DIFFRACTION ANALYSIS

Because it affords rapid data generation, XRD constitutes our scheme for monitoring the transient evolution of iron ash. Like Mossbauer analysis, XRD is accurate over a range of sample compositions, but it permits an analysis with only 20 mg of iron ash and takes only three hours. Furthermore, XRD costs us \$15 per analysis, as compared with \$200 for Mossbauer under contract. Moreover, the peak overlaps on Mossbauer spectra often make them more difficult to resolve than XRD patterns. Existing XRD techniques merely have to be adapted to our needs. These XRD techniques are thoroughly treated in the classic 1954 text by Klug and Alexander [14]. As a supplemental reference, Cullity [15] is recommended, for it describes developments in the 24 years subsequent to Klug and Alexander's text.

XRD patterns represent the intensity of diffracted X-rays ($\text{Cu K}\alpha$ in our instrument) versus 2θ , the diffraction angle. The positions and relative intensities of certain peaks identify specific minerals, while peak heights indicate mass concentrations with reference to calibration standards. The quality of XRD is very sensitive to sample preparation. In powdered samples, the grain size must be small enough to avoid preferred orientation yet the crystallite (coherent crystal domain on a grain) size must be large enough to prevent line broadening.

Three methods are conventionally used for quantitative determinations of the composition of polycrystalline materials from XRD patterns. The external standard

method uses the diffraction peak from a pure component as a reference and is suitable only for binary-phase mixtures. The direct comparison method uses a line from a single component in the mixture, but the calibration curve is derived from theoretical calculations, not measurements. The internal standard method uses a line from a foreign material added to the mixture in known quantities. Because the external standard and direct comparison methods are highly affected by changes in the physical properties of a mixture (for example, grain size) as well as the diffractometer's settings, the internal standard method constitutes the most reliable conventional calibration scheme. Nevertheless, a new scheme, the intrinsic standard method has to be derived for our applications, to avoid the peak overlap introduced by the internal standard. The intrinsic standard scheme uses the diffraction peak from a component of the mixture as the reference, and the calibration curve is empirically derived.

Because of XRD's simplicity, only two problems arise in our applications: (1) peak overlap among the important mineral species, and (2) interference from the carbon matrix.

4.3 PEAK ASSIGNMENTS

XRD patterns are obtained using the Rigaku rotating anode X-ray generator (60kV, 300mA maximum output) and the Huber diffractometer. Peaks in the XRD spectra often overlap when the mineral compositions are as similar as those of the iron compounds we hope to identify. Of course not all the peaks from a particular specie need be isolated, so long as one strong, isolated peak from each mineral is observed. Once the phases are identified, their concentrations can be determined, even if their peaks overlap, by deducing the appropriate linear combinations of peak heights for the constituents.

Two synthetic mixtures are adequate to demonstrate satisfactory separation of peaks. The paper from the group at Physical Sciences Inc. [7] includes observed and equilibrium product distributions for pyrite oxidation at typical p. f. firing conditions. The major pyrite derivatives in the products are Fe_{1-x}S and Fe_3O_4 , and, to a lesser extent, FeS_2 , Fe_2O_3 , and Fe_{1-x}O . We formed a carbonaceous mixture from which we decided to omit FeS_2 , because we had already established that our char's FeS_2 inclusions are all converted to Fe_{1-x}S during char synthesis. Our non-carbonaceous

mixture, on the other hand, contained pyrite, in anticipation of our extraneous pyrite studies.

In our carbonaceous sample, pulverized synthetic carbon was added to form a mixture composed of 8% Fe_{1-x}S , 5% FeO , 29% Fe_3O_4 , 6% Fe_2O_3 , and 52% C. The proportions of total mineral matter to carbon are consistent with extents of burnout between 80 and 90%. The XRD pattern appears in Fig. 4.1. The diffraction pattern spans 2θ values from 20 to 70 degrees, and the peaks are labelled by mineral specie as follows: P(yrrhotite, Fe_{1-x}S), W(ustite, FeO), M(agnetite, Fe_3O_4), H(ematite, Fe_2O_3), and C(arbon, C). As expected, there is some overlap, including the three peaks with the highest intensities. But there are also isolated peaks for each of the relevant species at adequate intensities. We plan to use the following assignments: W = 42, M = 43, P = 44, and H = 50.

Figure 4.1 X-ray diffraction pattern from a mixture of iron compounds and pulverized synthetic carbon. The mixture composition is 8% Fe_{1-x}S (P), 5% FeO (W), 29% Fe_3O_4 (M), 6% Fe_2O_3 (H), and 52% C (C).

Thus, a scan of 2θ values from 36 to 51 degrees is also sufficient to demonstrate adequate resolution in the non-carbonaceous sample. Shown in Fig. 4.2 is the XRD pattern for a mixture comprising FeS_2 , Fe_{1-x}S , FeO , Fe_2O_3 , and Fe_3O_4 . Evidently, the addition of pyrite does not degrade the peak resolution, and the 2θ value of 47 degrees is assigned to pyrite.

Figure 4.2 X-ray diffraction pattern from a mixture of FeS , FeS_2 , FeO , Fe_2O_3 , and Fe_3O_4 . Labelled are only those peaks that are used for quantitative determinations of composition.

4.4 SAMPLE PREPARATION

4.4.1 Carbon-Free Samples

XRD is highly sensitive to sample preparation in two regards. First, the specimen used in the analysis must constitute a representative sample of the bulk materials. This is best achieved by alternately mixing and grinding the bulk materials before extracting a specimen. After a representative powder specimen is secured, its XRD pattern should be reproducible.

Reproducibility imposes two stipulations of its own. First, the sample's grains must be randomly oriented for reproducible peak heights. Magnetic materials must not be permitted to align during sample preparation, and this demands a sufficiently viscous binding agent for the powder. More generally, grain sizes must be small enough to permit a large number of differently-oriented grains to be simultaneously sampled. Typically, with rotating sample mounts, a mean grain size of 45 microns is usually small enough, although for species with highly symmetrical structures like iron compounds, 75 microns is fine enough. With stationary mounts, typically, grain sizes of about 10 microns are desirable. The other stipulation for reproducibility consists of preventing variable line broadening and attendant height shortening. To prevent line broadening altogether, the crystallites must be larger than approximately 0.1 microns.

Of course, the preceding are merely general guidelines, as any sample preparation scheme utilized should be empirically tested. For the scheme described in Sec. 4.5, the relative heights of the peaks of interest (except for FeO) are typically reproducible to within 5%.

4.4.2 Carbonaceous Samples

The XRD pattern from the 63-125 micron microporous synthetic char loaded with about 10% pyrite appears in Fig. 4.3. Despite the range of signal fluctuations, little structure is evident because this diffraction pattern is dominated by the interference from carbon. Actually the inclusions in the sample also contribute, particularly as the peak at 44 degrees. This peak is due to pyrrhotite, not pyrite. In the curing stages of the char synthesis, temperatures are high enough to convert all pyrite into pyrrhotite, so the spectra is plausible, albeit too noisy for quantitative analysis.

Figure 4.3 X-ray diffraction pattern of 63 to 125 micron char of 10% pyrite loading. The mineral peaks are indistinguishable from the carbon background.

The carbon could be removed from the ash prior to analysis by either low temperature plasma ashing or chemical dissolution. Ashing might induce chemical transformations, and chemical dissolution of carbon involves reagents strong enough to dissolve minerals too. Generally speaking, any scheme to eliminate the carbon matrix will also affect the mineral inclusions.

Fortunately, this problem has been faced before and solved by simply grinding the carbon into the range of several microns. Grinding exposes the mineral inclusions, enhancing their contributions to the diffraction pattern. The patterns in Figs. 4.4 and 4.5 illustrate the best improvements attainable by using our pulverizer. The sample in Fig. 4.4 was pulverized once at 2 tons then twice at 5 tons. While the general shape of the diffraction pattern resembles the diffraction pattern in Fig. 4.3 for the unpulverized sample, distinct peaks are seen clearly. In fact, the peaks at 30, 34, 44, and 53 degrees are all attributable to pyrrhotite.

Figure 4.4 X-ray diffraction pattern of 63 to 125 micron char of 10% pyrite loading after mild pulverization (1X at 2 tons, followed by 2X at 5 tons). Note the Fe_{1-x}S peaks at 2θ values of 30, 34, 44, and 53 degrees.

Figure 4.5 X-ray diffraction pattern of 63 to 125 micron char of 15% pyrite loading after intense pulverization (2X at 15 tons). Note the Fe_{1-x}S peaks at 2θ values of 30, 34, 44, and 53 degrees.

The sample in Fig. 4.5 was pulverized differently - twice at 15 tons - and also contains 15% pyrite (vs. 10% for Fig. 4.4). The harsher pulverization does little to improve the background noise.

Grinding the char by hand surprisingly leads to a smaller particle size distribution. Compared in Fig. 4.6 are the mass-based size distributions (using a 280 micron orifice tube) of glassy carbon initially size classified to 90 to 106 microns after hand grinding vs. pulverization. In a ceramic mortar and pestle, 40 mg of char was ground 5 times using 10 turns of the wrist each time. For comparison, 30 mg of char was pulverized 4 times at 15 tons. Surprisingly, the hand grinding achieves a lower median size, 23 microns compared with 49 microns for the pulverizer. Furthermore, the hand grinding is reproducible. In the future, 40 mg of char pregrinding will be ground by hand with intermittent stirring.

Figure 4.6 Mass-based cumulative size distribution of 90 to 106 micron glassy carbon after grinding. Hand grinding with mortar and pestle (solid line) is compared with pulverization at 15 tons for 4X (dotted line).

4.5 INTRINSIC STANDARD METHOD OF CALIBRATION

After a sample's XRD pattern is obtained, the peak heights must be used to determine the composition. Due to their sensitivity to machine settings and sample physical properties, the direct comparison and the external standard methods do not constitute adequate calibration schemes. Also, the addition of foreign material to our sample introduces an irresolvable peak overlap, which makes the internal standard method unsuitable for our studies.

We therefore developed an intrinsic standard calibration scheme that utilizes a reference that is already a component of the sample to be analyzed. In this scheme, the concentration of each phase is empirically determined relative to that of one of the constituents. The concentration of the reference is determined by difference. By using the software routines "POWDER" to perform a background fit and "PEAKS" to determine peak heights on the XRD patterns, we developed a scheme for non-carbonaceous samples. The broad carbon peak renders peak resolution intractable for carbonaceous materials, and other software routines were explored for this purpose. The search for better software led to the finding of a simpler single-axis diffractometer and accompanying software that could supersede the first X-ray system. A discussion of the new system and preliminary work accomplished is in section 4.7.

In our calibration schemes, Fe_3O_4 and Fe_{1-x}S constitute the reference species, because one of them is always expected in our ash. Non-carbonaceous samples containing uncorrelated amounts of FeS_2 , Fe_{1-x}S , FeO , Fe_2O_3 , and Fe_3O_4 were used to develop calibration curves. Unfortunately, a calibration curve cannot be established for FeO because, as Fig 4.7 shows, its diffraction intensity does not vary monotonically with concentration. Nevertheless, this should not pose a major problem, because FeO is not expected to be a major constituent in our ash [7].

In Fig. 4.8 the calibration curves are graphed against log axes, to allow easier perception of their accuracy over a wide range of concentrations. These curves possess linear correlation coefficients that supersede 99%; nevertheless, cubic polynomials provide better fits than straight lines. The equations for the various calibration curves are listed in Tab. 4.1, along with the range of relative concentrations for which they apply. When evaluated against synthetic mixtures, these calibration curves are typically accurate to within 5% relative, as demonstrated by Tab. 4.2. Tab. 4.2 shows the inferred compositions from two mixtures. For the first mixture, three specimens were prepared and analyzed twice each; for the second mixture, only two specimens were prepared, but they were also analyzed twice. The greatest errors occur in the inferred FeS_2 concentration, at values below 20 wt%.

Figure 4.7 Concentration of FeO for various X-ray diffraction intensities, relative to Fe_{1-x}S (solid curve) and Fe_3O_4 (dotted curve).

Figure 4.8 Intrinsic standard calibration curves for x-ray diffraction analysis of extraneous pyrite. Shown are curves for Fe_{1-x}S (square), FeS_2 (triangle), Fe_2O_3 (circle), and Fe_3O_4 (diamond) relative to Fe_{1-x}S (solid curves) and Fe_3O_4 (dotted curves). Cubic polynomials are used for all fits.

Table 4.1 Calibration Equations for X-Ray Diffraction Analysis
(relative concentration, *c*, as function of relative intensity, *I*)

<u>Compound</u>	<u>Reference</u>	<u>Calibration Equation</u>	<u>Range</u>
FeS ₂	Fe _{1-x} S	$-0.0732+2.52I+0.229I^2-0.0440I^3$ 0.119< <i>c</i> <12.4	0.0627< <i>I</i> <4.81
		$-0.135+2.82I+0.0173I^2-0.0121I^3$ 0.119< <i>c</i> <16.7	0.0627< <i>I</i> <7.3081
	Fe ₃ O ₄	$-0.00274+0.460I+0.839I^2-0.404I^3$ 0.0654< <i>c</i> <1.28	0.123< <i>I</i> <1.62
Fe ₂ O ₃	Fe _{1-x} S	$0.0244+1.50I+4.69I^2-2.84I^3$ 0.0695< <i>c</i> <0.946	0.0268< <i>I</i> <0.3343
	Fe ₃ O ₄	$-0.0638+1.19I-0.809I^2+0.413I^3$ 0.0642< <i>c</i> <0.990	0.114< <i>I</i> <1.27
Fe ₃ O ₄	Fe _{1-x} S	$0.192-2.98I+33.1I^2-49.2I^3$ 0.139< <i>c</i> <1.10	0.0764< <i>I</i> <0.35
		$0.587+1.52I+1.76I^2-0.359I^3$ 1.10< <i>c</i> <10.1	0.35< <i>I</i> <2.97
Fe _{1-x} S	Fe ₃ O ₄	Invert equation for Fe ₃ O ₄ referenced to Fe _{1-x} S	

Table 4.2 Intrinsic Standard Determinations of Composition of Synthetic Mixtures

<u>Trial</u>	<u>Weight Percent of Phases in Fe_{1-x}S-FeS₂-Fe₂O₃-Fe₃O₄ System</u>			
	<u>Fe_{1-x}S</u>	<u>FeS₂</u>	<u>Fe₂O₃</u>	<u>Fe₃O₄</u>
Actual Composition:	33	22	11	33
A1*	33	22	11	34
A2	32	22	12	35
B1	32	24	11	34
B2	32	24	11	33
C1	32	23	12	33
C2	31	24	12	34
Actual Composition:	66	11	11	12
D1	65	14	10	11
D2	69	11	10	11
E1	64	14	10	11
E2	64	15	10	11

* Letter and number identify sample and analysis, respectively

For FeO, reasonable estimates of the concentration can be achieved by adding a known amount of Fe_{1-x}S or Fe_2O_3 as an internal standard. These two phases are selected because at least one of them is expected to be absent when FeO is observed. After adding a known amount of internal standard to a known amount of sample, the intrinsic standard calibration curves can be used to determine the ratio of the internal standard's concentration to those of the other calibrated species. The amount of FeO is, subsequently determined by difference. Of course, errors in the concentrations of the other phases accumulate in the inferred FeO concentration.

Shown in Tab. 4.3 are the inferred FeO concentrations for two mixtures containing 10.0 and 9.7 wt% FeO. Three and two specimens were prepared for the first and second mixture, respectively, and each specimen was analyzed twice. For the first mixture, Fe_2O_3 is a more accurate reference, whereas for the second mixture, Fe_{1-x}S is more accurate. That is probably because the second mixture contains twice as much Fe_{1-x}S as the first mixture.

Table 4.3 Internal Standard Determinations of FeO Content of Synthetic Mixtures

<u>Trial</u>	<u>Actual Composition</u>	<u>FeO Weight Percent</u>	
		<u>Fe_{1-x}S Standard</u>	<u>Fe_2O_3 Standard</u>
A1*	10.0	7.7	9.2
A2	10.0	6.7	11.5
B1	10.0	5.3	7.9
B2	10.0	5.2	8.1
C1	10.0	4.8	14.6
C2	10.0	2.1	14.9
D1	9.7	7.3	4.1
D2	9.7	13.0	1.9
E1	9.7	7.1	4.7
E2	9.7	6.7	2.5

* Letter and number identify specimen and analysis, respectively

Finally, in Fig. 4.9 is shown the calibration curve for FeS_2 referenced to Fe_{1-x}S , used for our pyrolysis studies. Plotted is the relative concentration of FeS_2 versus relative intensity. When the composition of synthetic mixtures are inferred on the basis of this curve, the error is typically under 5% relative (see Tab. 4.4).

Figure 4.9 X-ray diffraction calibration curve for various FeS_2 : Fe_{1-x}S ratios.

Table 4.4 Intrinsic Standard Determinations of Fe_{1-x}S Content of Synthetic Mixtures

<u>Fe_{1-x}S Weight Percent of Fe_{1-x}S-FeS_2 System</u>	
<u>Trial</u>	
Actual Composition:	60
A1*	60
A2	60
B1	58
B2	57
C1	58
C2	56
Actual Composition	85
D1	82
D2	87
E1	82
E2	81

* Letter and number identify specimen and analysis, respectively

4.6 ADOPTED X-RAY DIFFRACTION SCHEME

The findings in the preceding sections were utilized to develop a chemical analysis procedure for the condensed phase products of extraneous pyrite combustion. Following is the scheme:

Sample Preparation

1. Obtain approximately 30 to 100 mg of sample.
2. If the sample is a synthetic mixture, place it in a vial and mix for 10 minutes using a mechanical shaker.

3. Grind the sample in a ceramic mortar and pestle by hand using 10 revolutions of the wrist each time. If the sample is a calibration standard (typically already under 10 micron in particle size), grind 5 times. If it is an experimentally derived residue (typical particle size of 10 to 20 microns), grind 7 times.

4. Preheat a hot plate for 4 minutes before using it at a setting of 4 (medium high).

5. Place about 25 mg of the sample on a 2 cm square silicon wafer. Add 1 drop of the binding agent nitrocellulose-in-amyacetate with the butt of a Q-tip. Stir to obtain a topographically smooth spot of about 1 cm square. The sample should be viscous enough to resist the alignment of magnetic phases.

6. Dry off the binding agent by holding the wafer approximately 4 to 6 inches above the hot plate. The hot plate should be set so that the sample dries in 1 minute.

X-Ray Scan on the Huber Diffractometer

7. Set the slit widths to 4 mm (horizontal) and 10 mm (vertical).

8. Place and align sample on sample holder.

9. Set power to 45 kV and 50 mA.

10. Scan 2θ values from 20 to 60 degrees, at 0.1 degree increments, for 5 second count times. This is a broad scan to confirm that only the expected phases are present.

11. Scan 2θ values from 36 to 51 degrees, at 0.1 degree increments, for 60 second count times. This is the scan to use for quantitative analysis.

Peak Resolution

12. Use the "POWDER" software to fit a constant value background to the XRD pattern. All of the software mentioned are obtained from Dr. Glenn Waychunas at Stanford University's Center for Materials Research.

13. Use the the noise option of the "PEAKS" software to identify peak heights, with the background value from "POWDER". Calculate the net peak heights.

14. Normalize with respect to reference line of calibration standards (Fe_{1-x}S and Fe_3O_4) to obtain relative concentrations.

4.7 NEW XRD ANALYSIS SYSTEM

In addition to better peak finding and background fitting software, the new XRD analysis system requires little sample preparation, needs no re-alignment of the sample platform and it contains slits of constant width. The new system, under the supervision of Professor Bruce Clemens, is found in the Material Science and Engineering Building. It consists of a Phillips 3100 XRG X-ray generator and powder diffractometer, data acquisition and transfer equipment, and supporting computer and software. The pertinent software are Micro-Peak and Micro-ID that were developed by Materials Data, Inc (MDI) for the sole purpose of analyzing powder diffraction patterns. Among its many capabilities, Micro-Peak takes the diffraction data and finds all the discernable peaks, subtracts the background, and calculates the area of the peaks. Micro-ID compares the diffraction pattern to standard diffraction patterns and lists all the possible species matches.

The Phillips powder diffractometer is better suited for our iron sulfide studies than the present Huber diffractometer. In powder diffraction, only one axis of movement between the source, the sample and detector is needed for a scan. The Huber complicates the analysis with four axis of movements while the Phillips uses only one. The Phillips diffractometer is designed with constant distances between the source, sample and detector. This eliminates the problem of constant re-alignment with the Huber diffractometer. And finally the Phillips constant width slits insure that identical conditions are used for each diffraction scan.

As an example of the capability of the new system Fig. 4.10 shows the full diffraction scan of pyrite for the lowest possible count time. It is seen that a high signal-to-noise ratio and a constant background can be achieved even for a low count time. To test the reproducibility of the new system calibration runs were performed with pyrrhotite and pyrite and are presented in the next section.

4.7.1 Calibration of Iron Sulfide Phases

As in the calibration procedure discussed above, the following improved procedure uses the intrinsic standard method to relate the peaks of each species to their concentration in the sample. Two improvements are that the areas of the peaks are used, as opposed to the heights, and that two calibration curves are used instead of one. The areas are chosen because the integrated area of a particular peak gives a better representation of the concentration of the species. The height could be used instead if all peak widths were equal, which is not the case for the iron sulfides. To circumvent the use of log scales for the area ratios versus concentration ratios, the ratios are taken such that they remain between zero and one. At low pyrite concentrations the ratio of pyrite to pyrrhotite is plotted in one graph and at high concentrations of pyrite, the ratio of pyrrhotite to pyrite is plotted.

Figure 4.10. Powder Diffraction Scan of Pyrite (40 kV 20mA)

During initial calibration runs with pyrite and pyrrhotite, difficulties arose with the pyrrhotite peak at $2\theta = 43^\circ$. As seen in Fig. 4.11, the 43° peak has two convoluted peaks that could be due to preferred orientation of the pyrrhotite crystals on the specimen slide. To eliminate the problem, a new peak at $2\theta = 53.2^\circ$ was chosen for the pyrrhotite to pyrite comparison. As shown in Fig. 4-12, the double peak does not appear at this angle.

Figure 4.11. 43° Diffraction Peak of Pyrrhotite (40kV 20mA)

Figure 4.12. 53° Diffraction Peak of Pyrrhotite (40kV 20mA)

The two calibrations are seen in Figs. 4-13 and 4-14. Since both curves fail to be monotonic there still exists a difficulty in the procedure. Possible remedies include: placing the sample in a plastic boat that will give the sample more depth in the X-ray beam and prevent preferred orientation; and to use longer count times. The first remedy will introduce small absorption errors that may or may not be significant.

XRD Calibration: Pyrrhotite to Pyrite

Figure 4.13. X-ray Diffraction Calibration Curve: Pyrrhotite to Pyrite

XRD Calibration: Pyrite to Pyrrhotite

Figure 4.14. X-ray Diffraction Calibration Curve: Pyrite to Pyrrhotite

4.7.2 New X-ray Diffraction Scheme

The following scheme is similar to the first method but there are important changes.

Sample Preparation

1. Obtain approximately 40 to 60 mg of sample.
2. If the sample is a synthetic mixture, place it in a vial and mix for 10 minutes using a mechanical shaker.
3. Grind sample in a mortar and pestle by hand using 10 revolutions of the wrist each time. If the sample is a calibration standard, grind 5 times. If it is an experimentally derived residue, grind 7 times.
4. Place double-stick tape and a shortened microscope specimen slide.
5. Spread sample evenly on tape with the wooden end of a cotton swab.

X-ray Scan on the Phillips Powder Diffractometer

6. Place sample into holder.
7. Set power to 40kV and 20mA.
8. Scan 2θ from 45° to 55° , 0.1° steps and 10 second count times.

Peak Resolution

9. Use Micro-Peak to subtract background, perform a K-alpha 2 elimination, find peaks, and calculate areas of peaks. (Use parabolic background subtraction with 5 segments forward and one back, and Rachinger K-alpha 2 elimination correction.)
10. Use Micro-ID to compare scan to standard diffraction patterns for identification.

CHAPTER 5

THERMOCHEMICAL CALCULATIONS

5.1 INTRODUCTION

Another aspect of the research program is reliable thermochemical calculations for iron ash species at typical combustion conditions. The equilibrium product distributions will be compared to the distribution of mineral species observed in the laboratory for ranges of temperature, reaction time, and oxygen level. In this sense, they constitute a gauge for kinetic restrictions in the conversion rates, if any are present. This is an important step toward predicting ash compositions from mineral matter compositions.

To achieve reliable thermochemical calculations, an existing computer simulator had to be modified to handle the Fe/O/S thermochemistry. This chapter is devoted to comparisons among our results obtained with the modified simulator and reported values, with a particular emphasis on the sensitivity to the number of species included in the calculation. The pyrite phase diagram and iron oxide ash conversions are considered. Finally, baseline information on pyrite pyrolysis and oxidation is presented. In the next chapter, the pyrolysis results are compared with laboratory studies.

5.2 THE MODIFIED STANJAN SIMULATOR

The primary modeling tool we adapted to pyrite thermochemistry is the STANJAN thermochemical equilibrium solver developed by Prof. William C. Reynolds at Stanford [24]. STANJAN is a PC-driven interactive program based on the method of element potentials, which assigns the minimum of the Gibbs free energy using undetermined multipliers. This strategy generally involves far fewer unknowns in the algorithm than conventional solvers, because the element potentials of the constituent atoms and the molar amount in each phase are the only variables. Several phases, including many condensed phases, are permitted, although only ideal gas and ideal solution behavior are described. The current version handles a total of 20 species in up to six phases containing eight elements, but expansions to larger systems are easily implemented.

The thermodynamic properties are prepared from digitized versions of the JANAF tables. The standard enthalpies of formation, net enthalpy differences, and entropies are obtained by interpolations to the system temperature, as required.

While the underlying computational strategy in this code is ideal for our application, it has one major limitation: only integer values can be assigned to the atomic proportions of the various species. Pyrrhotite, for one, is clearly not compatible with this. Without going into further detail, our modifications eventually yielded a revised simulator, called STANJANR, which relaxes it.

5.3 COMPARISONS WITH HIGH TEMPERATURE IRON OXIDE ASH THERMOCHEMISTRY

The most directly relevant equilibrium product distributions were reported recently by Huffman et al. [7]. They resolve condensed species in the Fe/O/S system into five species: pyrrhotite ($\text{Fe}_{0.877}\text{S}$), hematite (Fe_2O_3), magnetite (Fe_3O_4), molten iron sulfide (FeS(l)), and molten iron oxide (FeO(l)). High temperatures are emphasized, covering the range from 1000 to 1800 K, and the fuel equivalence ratio is also varied over a wide range.

Before proceeding to the direct comparisons, it should be noted that the distribution of iron reported for their 1300K case did not sum to one hundred percent, and was altered slightly to close the deficiency. The original results for this case appear in Fig. 5.1, while the revised values are seen in the comparison with our values in Fig. 5.3. In this figure it is seen that closure is violated only for oxygen to pyrite mole ratios greater than 2.2. The gaps were rectified by adjusting the amounts of the molten iron sulfide.

Figure 5.1 Calculated equilibrium iron phase percentages as a function of oxygen level at 1300 K (from Huffman, original).

There is also a second preliminary caveat; viz. Huffman et al. did not explicitly report the set of oxysulfide species in the gas phase, or which combination of condensates were used in the various phases. Our results were brought into agreement with theirs by including the following gases: O_2 , S_2 , SO_2 , SO , and S . The condensates, $Fe_{.877}S$, Fe_2O_3 and Fe_3O_4 , had to be handled as three separate phases, while $FeO(l)$ and $FeS(l)$ appear in a single melt phase. In addition to showing which species to use in the computations, this series of "matching" runs revealed the importance of including as many of the relevant species as possible because omissions will give misleading results.

Comparisons between reported results and those based on STANJANR appear in Figs. 5.2 – 5.5. In all cases the proportions of iron among the various condensates are plotted versus the ratio of atomic oxygen to pyrite, to represent variations in the equivalence ratio. Before turning to aspects of the formal comparisons among the calculations, some general tendencies are worth reiterating. The first decomposition product of pyrite, pyrrhotite, is absent at any equivalence ratio for all temperatures above 1300K. And the molten phase forms only at fairly high temperatures, in so far as it is absent at 1000K. While magnetite is usually present at almost all operating conditions, hematite is only present at mole ratios of 2.6 and higher, except at 1800K.

Results from STANJANR compare very favorably with Huffman et al.'s at 1000 K, as seen in Fig. 5.2. Similar agreement is recovered at 1800K, in Fig. 5.5, although the discrepancies are more noticeable but still tolerable. Also, the discrepancies in the two amounts of the molten phase for mole ratios greater than 2.2 are not due to any gross problems with either equilibrium solver. Rather, they are due to the fact that the Huffman calculations were performed at fewer points, so their resolution of this stage is much coarser than ours.

Although the behavior is considerably more complicated at 1500 K, the agreement in Fig. 5.4 is again very close. However, these simulations were more troublesome than the others, in that the calculation failed to converge for mole ratios between 1.76 to 2.12 mol O_2/FeS_2 . Evidently the very dramatic decline in the amount of iron in the iron oxide melt near the mole ratio of 2.1 is difficult to compute. As explained later, we have seen other indications that convergence problems are often encountered when there are very small amounts of any of the reaction species.

The results at 1300 K, in Fig. 5.3, do not match well with the corresponding points in Huffman's paper, especially for mole ratios from unity to 1.8. General tendencies are very similar, but significant quantitative discrepancies are seen in all of the reaction species. Here again, the coarse resolution and curve fits in the published results are factors, particularly for magnetite. But deviations in the amounts of pyrrhotite and the FeS-FeO melt phase can not be rationalized this way.

Figure 5.2 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1000 K. (Symbols = STANJANR, lines = Huffman)

Figure 5.3 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1300 K. (Symbols = STANJANR, lines = Huffman)

Figure 5.4 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1500 K. (Symbols = STANJANR, lines = Huffman)

Figure 5.5 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1800 K. (Symbols = STANJANR, lines = Huffman)

While nominally troublesome, we do not think that these discrepancies reflect any flaw in STANJANR. It seems more likely that they manifest an acute sensitivity to the set of condensates included in the calculation. In other words, the appearance or disappearance of any specie depends on which other species are present. This point is clarified in the following study.

The cases in Figs. 5.2–5.5 above were not computed with all of the five condensates in the reaction system (although all of the aforementioned gases were always present). By a process of trial and error we found the best agreement with the published results obtained for the following systems: at 1000K, both molten species were omitted; at 1300K, the pyrrhotite was substituted by magnetite for mole ratios above 1.5; at 1500K, pyrrhotite was omitted; and, at 1800K, neither pyrrhotite nor hematite were included.

While this procedure is arbitrary, it is required to match the reported compositions. This is demonstrated by comparing the respective results in Figs. 5.6–5.8 with those in Figs. 5.2–5.5 for the same conditions. Note especially that results in Figs. 5.6–5.8 represent the behavior when all five condensates are included. First, it is evident that some cases are very close, namely those for 1000 and 1800K; in fact, the deviations can all be explained by the coarse resolution in the published cases. But for the 1300K case, in Fig. 5.6, the discrepancies are very significant. The two liquid phases are not present at all for O_2 to FeS_2 mole ratios of 0.9 through 2.6 when the magnetite is included, as in Fig. 5.6, whereas in the earlier case, Fig. 5.3, the liquid melts appeared in this range when magnetite was omitted. The case at 1500K failed to converge for most equivalence ratios when all condensates were included.

Figure. 5.6 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1300 K (all condensates considered).

Figure. 5.7 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1000 K (all condensates considered).

Figure. 5.8 Comparison of STANJANR & Huffman equilibrium iron phase percentages at 1800 K (all condensates considered).

We conclude that the modified equilibrium solver does, in fact, give meaningful results for Fe/O/S thermochemistry, which generally reproduced published behavior at typical combustion conditions. However, the inclusion and especially the exclusion of certain species has a marked effect on the final results. In addition, it does indeed matter which condensates are combined in each phase. Because most gases can be assumed to be miscible in each other they can be placed in a single phase. The condensates, in contrast, are not always miscible in each other and in some cases must be considered as a separate phase.

5.4 CONVERGENCE AND SPECIFICATION OF THE PRODUCT PHASES

As mentioned earlier there was a convergence problem at 1500 K in a broad range of equivalence ratios. Math overflow run-time errors often accompanied convergence problems, suggesting that the amounts of specific condensates were becoming miniscule. After trying to modify the code to eliminate this defect, we eventually concluded that it would be much more expedient to simply screen particular cases, and then alter the species in the calculation so as to yield a converged solution, according to the following scheme:

1. Include all possible species for a particular set of atoms in the species data file.
2. Put all gaseous species, O_2 , S_2 , SO_2 , SO and S , into one phase.
3. Put each solid condensate into a separate phase.
4. Put the liquid condensates into every possible combination of liquids from single liquid phases to all liquids in one phase.
5. Compute the equilibrium product distribution for the desired operating conditions.
6. If the computation does not converge, run conditions around the troublesome region. Remove all liquid phase species present in negligible amounts. If it still fails to converge, then remove all condensates which are present in very low concentrations. We have not encountered any cases which fail converge after these steps have been taken.

Figure 5.9 Pyrite Phase Diagram [25].

5.5 THE PYRITE PHASE DIAGRAM

STANJANR was used in another set of computational runs to attempt to duplicate various points in an Fe-S phase diagram, which appears in Fig. 5.9. Before the results are presented, a few words about the assumptions must be made. First of all, the "liquid" phase found in the diagram consisting of iron and sulphur in varying proportions was modeled as a phase of Fe(l) and S(l). At about 39 weight percent of sulphur a line labeled Fe_{1-x}S is essentially vertical up to a temperature of 700 C. Strictly speaking, the composition of this specie varies continuously, although it remains very similar to the pyrrhotite composition, $\text{Fe}_{.877}\text{S}$, found in the data file. With this in mind, our calculations used the properties of $\text{Fe}_{.877}\text{S}$ throughout this range. The remainder of the diagram was modeled as shown on the figure. The species considered in each of the runs were FeS_2 and $\text{Fe}_{.877}\text{S}$ in separate phases, and Fe(l) and S(l) in a single phase. The results of these runs are found in Table 5.1.

Comparing the data from the phase diagram and the results from the calculations it is seen that, in the region considered, the two give species mass fractions which are within 3% of each other. The most promising result is that the disappearance of $\text{Fe}_{.877}\text{S}$ and the appearance of FeS_2 occur between 50 and 60 wt% S, as seen in the phase diagram.

[Wt% S, T (K)]	Species Mass Fractions							
	FeS ₂		Fe _{.877} S		Fe (l)		S (l)	
[45, 773]	.39	(.38)	.61	(.62)	0	(0)	0	(0)
[45, 873]	.39	(.38)	.61	(.62)	0	(0)	0	(0)
[50, 773]	.75	(.77)	.25	(.23)	0	(0)	0	(0)
[50, 873]	.75	(.77)	.25	(.23)	0	(0)	0	(0)
[60, 773]	.86	(.85)	0	(0)	.52e-10	(0)	.14	(.15)
[60, 873]	.86	(.85)	0	(0)	.20e-8	(0)	.14	(.15)
[70, 773]	.64	(.64)	0	(0)	.13e-9	(0)	.36	(.36)
[70, 873]	.64	(.64)	0	(0)	.51e-8	(0)	.36	(.36)
[80, 773]	.43	(.42)	0	(0)	.21e-9	(0)	.57	(.58)
[80, 873]	.43	(.42)	0	(0)	.83e-8	(0)	.57	(.58)
[90, 773]	.21	(.21)	0	(0)	.22e-9	(0)	.78	(.79)
[90, 873]	.21	(.21)	0	(0)	.11e-7	(0)	.78	(.79)

Table 5.1 Pyrite Phase Diagram Duplication (STANJANR results followed by pyrite phase diagram data in parenthesis).

5.6 BASELINE INFORMATION

5.6.1 Pyrite Pyrolysis

Equilibrium compositions were determined for the operating conditions used in experiments. In keeping with the large uncertainty in the particle temperature, the calculations for each inlet gas composition have been repeated for broad ranges of temperature. The cases for pyrite pyrolysis are based on the following experimental conditions: 3.9 standard liters per minute of Argon gas and .667 grams per minute of pyrite particles, which correspond to 35.8 Argon atoms, 1 Iron atom, and 2 Sulfur atoms. These atom populations and the following product species were considered throughout the temperature range of 600 to 1000 K: FeS_2 , $\text{Fe}_{.877}\text{S}$, $\text{Fe}(\text{cr})$, $\text{FeS}(\text{cr})$, $\text{S}(\text{l})$, $\text{Fe}(\text{l})$, $\text{FeS}(\text{l})$, Ar , S_2 , and S . In some cases, some of the condensates had to be omitted to restore convergence, according to the procedure outlined above.

As seen in Fig. 5.10, the product composition is very simple, comprising only pyrite and pyrrhotite. At temperatures below 680 K only FeS_2 is present while at temperatures above 800 K only $\text{Fe}_{.877}\text{S}$. At intermediate temperatures the amount of FeS_2 gradually decreases while that of $\text{Fe}_{.877}\text{S}$ increases. All of these features are consistent with the product compositions assigned from the measurements, although we cannot yet assign the temperature range over which the transformation occurs.

Figure 5.10 STANJANR calculated equilibrium iron phase percentages as a function of temperature (pyrite pyrolysis).

5.6.2 Pyrite Oxidation

In these runs the same reactant flowrates are used but now oxygen is present in various concentrations. The oxygen levels were 6, 10, and 20 weight percent of total gas, which correspond to O_2 to FeS_2 mole ratios of 2.14, 3.58, 7.16, respectively. Adding oxygen entails many more product species; viz. $Fe_{.877}S$, Fe_3O_4 , Fe_2O_3 , $FeS(l)$, $FeO(l)$, FeS_2 , $Fe_{.947}O$, $Fe(cr)$, $FeS(cr)$, $S(l)$, $Fe(l)$, and, in the gas phase, Ar , O_2 , S_2 , SO_2 , SO , and S . The product distributions for these cases appear in Figs. 5.11-5.13.

In Fig. 5.11, the 2.14 O_2/FeS_2 case, Fe_2O_3 and FeS_2 are replaced with $Fe_{.877}S$ and Fe_3O_4 above 600 K, which vanish in turn above 1600 K. They are subsequently replaced by the FeS - FeO melt. As the fuel equivalence decreases, in Figs. 5.12 and 5.13, the same trend is observed. First, at a fairly low temperature, hematite is replaced by magnetite, which is then replaced by the melt phase at a higher temperature. The melt phase in this case is almost made up entirely of iron oxide. Both of these transition temperatures are shifted to higher values as oxygen is made more abundant. Note also that these distributions are not in keeping with the generic scheme so often applied to this system; i. e., pyrite to pyrrhotite, to the melt, to magnetite, to hematite. Of course kinetic restrictions might yield products which are much different than the corresponding equilibrium values, and these remain to be assessed.

Figure 5.11 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 2.14 O_2/FeS_2 .

Figure 5.12 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 3.58 O_2/FeS_2 .

Figure 5.13 STANJANR calculated equilibrium iron phase percentages as a function of temperature at a mole ratio of 7.16 O_2/FeS_2 .

CHAPTER 6

RESULTS AND DISCUSSION

6.1 INTRODUCTION

The components of our experimental system were integrated and utilized in a series of studies to confirm its viability. These studies constitute our initial attempt to delimit the operating domain that achieves the relevant thermochemistry. Since the technological operating domain that motivates our program covers the stages of pyrite chemistry preceding substantial magnetite formation, our initial studies focus on pyrolysis. Operating conditions for monitoring the complete progress of reaction are explored for both inert and oxidative pyrolysis in three radiant flow reactor studies. The first study seeks the widest range of furnace temperature compatible with pyrolysis in an inert atmosphere. The second study investigates conditions for monitoring the transients of inert pyrolysis. The final study assesses the impact of oxygen on the range of compatible furnace temperatures for achieving pyrolysis. An additional study was performed with a thermogravimetric analyzer to find the kinetic rate parameters for low temperature, low heating rate pyrolysis. These parameters are used in the PYRTEMP computer program to simulate the reactor studies and check their applicability to a higher heating rate case.

The reactor studies utilize the laboratory procedure described in previous sections. To circumvent the effects of associated carbon, the 20 micron extraneous pyrite particles described in Sec. 2.3.4 constitute the feed materials in these initial studies. The pyrite is subjected to simulated p.f. firing conditions in the radiant flow reactor at fixed feed rates of 0.18 g/min and 0.67 g/min for the inert and oxidation studies, respectively. The entrainment stream consists of pure argon in the inert studies, but contains 6% oxygen in the oxidative study. In the second inert study, the total gas flowrate is varied (and hence residence time) from 4 to 11 slm, but it is fixed in the other studies. For this variation in flowrate, the suspension loading ranges from 1.4×10^4 to 3.9×10^4 particles/cm³ and the interparticle separation ranges from 15 to 21 diameters.

After combustion, the ash is recovered and analyzed. Cross-section micrographs are used to monitor physical transformations. Chemical transformations of Fe/S/O phases are also monitored with X-ray diffraction analysis and in some cases yields are assigned gravimetrically. Finally, these concentrations are compared with thermochemical calculations in order to infer the kinetics constraints on pyrite transformations.

6.2 EXPERIMENTAL RESULTS

6.2.1 Physical Description of Ash

These results depict the transformation of pyrite under pyrolysis conditions for ranges of furnace temperature, nominal residence time, and ambient oxygen level. In the first series of experiments, the argon flow rate is fixed to achieve a nominal residence time of 725 ms for a range of furnace temperatures from 1125K to 1600K; in the second series, the gas flowrate is varied to attain nominal residence times from 250 ms to 725 ms at a fixed furnace temperature of 1610K. For these two studies, XRD analysis reveals only $\text{Fe}_{0.877}\text{S}$ and FeS_2 in the particulate phase, while elemental sulfur is recovered on the aerosol filters whenever pyrrhotite is observed. For the third study, however, trace amounts of magnetite are also observed and no sulfur is recovered until 1500K, due to the 6% ambient oxygen level. Furthermore, in this study, the nominal residence time is fixed at 725 ms for furnace temperatures ranging from 1160K to 1610K.

The cross-section photomicrographs in Figs. 6.1 to 6.3 monitor the evolution of pyrite during combustion. Fig. 6.1 establishes a reference, depicting unreacted pyrite particles. Fig. 6.1.A and 6.1.B are of 500X and 1250X magnification, respectively, and establish interparticle and intraparticle uniformity. The particles are angular and uniformly bright, a reflection of their homogeneous composition.

In the cross-section photomicrographs at 500X magnification in Fig. 6.2, however, compositional variations are evident. Shown are particles after 370 ms (Fig. 6.2.A) and 725 ms (Fig. 6.2.B) of inert pyrolysis at 1610K. At 370 ms, the particles are still angular. Highly microporous black rims are present on most particles, however, although their cores remain uniformly bright. The rims typically extend across less than one-fifth of the particle radii, and are slightly more extensive among smaller particles. The microporous rims advance radially inward with increasing time, so that they typically extend across one-half of the particle radii by 725 ms. Furthermore, by 725 ms, round, light-gray particles are present, but constitute less than one-tenth of the particles.

The impact of oxygen is demonstrated by the photomicrographs at 500X in Fig. 6.3. Shown in Figs. 6.3.A and 6.3.B are particles recovered after reaction at 1500K and 1610K, respectively, for 725 ms in 6% oxygen. The bulk composition of the sample in Fig. 6.3.A is the same as that of Fig. 6.2.B, with the addition of trace amounts of magnetite. The particle morphology is, however, different, for Fig. 6.3.A contains many more round particles. Furthermore, the round particles occur in two types, light-gray ones with uniformly dispersed pores and light-gray ones with uniformly dispersed grains of a dark-gray phase. Moreover, the angular particles' microporous rims now appear less dark.

Figure 6.1 Cross-section photomicrographs of unreacted pyrite particles.
(A) 500X magnification, establishing interparticle uniformity.
(B) 1250X magnification, establishing intraparticle uniformity.

Figure 6.2 Cross-section photomicrographs at 500X of pyrite particles after pyrolysis at 1610K.
(A) Nominal residence time of 370 ms.
(B) Nominal residence time of 725 ms.

Figure 6.3 Cross-section photomicrographs at 500X of pyrite particles after oxidative pyrolysis for nominal residence time of 725 ms.
 (A) Furnace temperature of 1500K.
 (B) Furnace temperature of 1610K.

Fig. 6.3.B shows that by 1610K, round particles now constitute over one-half of the sample. The round particles occur in four compositions: uniformly light-gray, light-gray with uniformly dispersed black pores, light gray with uniformly dispersed dark-gray grains, and uniformly dark-gray. Some of these round particles have large, round hollow regions that are usually close to their periphery. Most of the remaining angular particles are completely porous at this temperature.

6.2.2 Quantitative X-ray

The weight fractions of pyrrhotite in the samples collected at a fixed gas flowrate appear in Fig. 6.4 for furnace temperatures from 1125K to 1600K. The residence time is 725 ms, nominally, although it is decreasing for increasing furnace temperatures in this series. Nearly complete conversion is observed over this temperature range. There also seems to be two distinct stages of product formation. The first stage begins at 1125K and reaches a conversion of 12% pyrrhotite at about 1385K. It is followed by much more rapid conversion for higher temperatures, until 80% of the pyrite is converted in the available residence time by 1600K.

Figure 6.4 Weight fraction of $\text{Fe}_{0.877}\text{S}$ in pyrolysis products at various wall temperatures, 3.9 slm Ar, 0.8g FeS_2 /min.

Qualitatively similar behavior is seen in the data for various nominal residence times through at 1610K furnace, in Fig. 6.5. The conversion surges at 360 ms, after about 12% $\text{Fe}_{0.877}\text{S}$ has been formed.

Figure 6.5 Weight fraction of $\text{Fe}_{0.877}\text{S}$ in pyrolysis products at various cold gas residence times, 1610K wall temperatures, 0.8 g FeS_2/min .

A second set of pyrolysis experiments were performed to correlate the weight loss through the reactor and the pyrrhotite mass fractions. The median size of the particles were approximately 21 microns with a standard deviation of 5 microns. Both sets of pyrolysis data can be incorporated and used with the pyrite particle temperature model to assign kinetic rate parameters.

Fig. 6.6 shows the percentage mass loss of the condensed phases for various mean flow velocities. It should be noted that the mass loss curve was reduced by a constant value of 6.7 wt%, the average mass loss attributed to deposition in cold flow experiments and that mean flow rate is used over residence time because the residence time has not been measured. The dashed line at a mass loss of 23 wt% represents an upper bound for the ultimate yield of noncondensibles, assuming final products of $\text{Fe}_{0.877}\text{S}$ and S_2 . For the lowest flow rate, or longest residence time, the reproducibility of this ultimate value is fairly good as evidenced by the clustering of the three data points at this condition; the largest deviation is only 3 wt%. At progressively higher flow velocities, the mass loss monotonically decreases

as expected, but at 80 cm/sec there are three points which are clustered at 6 wt% and a fourth point about 1 wt%. Two of the three points at 6 wt% are believed to be a result of using a new quench nozzle that had not been "fouled" with molten pyrrhotite and sulfur aerosol. It is believed that some steady-state deposit must be reached to prevent additional accumulation on the nozzle and to minimize the losses to the system. The point at 1 wt% is believed to be a result of achieving the steady-state deposit and therefore is a better representation of the conversion at 80 cm/sec.

Figure 6.6 Fractional mass loss of the solid phase at various flow velocities for a wall temperature of 1626 K and a nominal number density of 12,000 #/cc.

The pyrrhotite mass fractions appear in Fig. 6.7. The mass fraction decreases for higher flow rates until at 80 cm/sec it rises. It is difficult to tell the exact fall-off of the mass fraction at the higher velocities because only one of the four points at this condition was X-rayed. The points in the extrapolated region involve intensity ratios that were beyond the range where the calibration was validated, and must range between 0.92 and 1.0. The point at 20 cm/sec that lies well below the extrapolated region could be a consequence of using iron (II) sulfide rather than pyrrhotite for the calibration. Recent X-ray scans with pyrrhotite indicated that the relative intensities at low pyrite levels are different for FeS and Fe_{1-x}S . Because higher relative amounts of pyrite gave similar relative intensities for the two iron sulfides, there is less uncertainty for lower Fe_{1-x}S mass fractions for this calibration curve.

Figure 6.7 Mass Fraction of $\text{Fe}_{0.877}\text{S}$ in condensed pyrolysis products at various flow velocities for a wall temperature of 1626 K and a nominal number density of 12,000 #/cc.

Conversion occurs in only one stage, however, in the oxidative pyrolysis data shown in Fig. 6.8. Although 12% yield is achieved at the same temperature as the inert case, the temperature range for significant pyrolysis is compressed by 100K to span from 1365K to 1500K. Apparently, the oxidation of evolved sulfur accelerates the pyrolysis, until 90% yield is reached at 1610K. In addition, the observed phases include trace amounts of magnetite starting at 1364K. moreover, the stoichiometry of pyrrhotite changes from $\text{Fe}_{0.877}\text{S}$ towards FeS, as evidenced by a progressive shift in the positions of the diffraction peaks.

Since the suspensions' temperatures are rapidly changing as they pass through the first half of the furnace, no simple relation among conversion furnace temperature, and nominal residence time would be expected. We emphasize the stages in the transient yields only because the break point coincides with a pyrrhotite composition of 12 wt.%. This proportion also coincides with a break point in the cumulative size distribution in Fig. 2.13, so the feature in the product compositions may simply be due to the variation of particle sizes in the feed. Of course higher particle temperatures and conversions would be expected for smaller particle sizes in this experiment.

Figure 6.8 Weight fraction of $\text{Fe}_{0.877}\text{S}$ in oxidative pyrolysis products at various wall temperatures, 3.9 slm of 6% O_2 -Ar, 0.67g FeS_2 /min.

6.2.3 Kinetic Rate Parameters for Pyrite Pyrolysis

Kinetic rate parameters, activation energy and frequency factor, were found for pyrite pyrolysis using the Perkin-Elmer TGS-2 thermogravimetric system, which monitors the weight loss with temperature rise, and a special heating-rate-based analysis technique. The system consists of a UU-1 temperature program controller, heater and balance control units, and an analyzer stand. Data acquisition and storage was performed with a Data Translation DT 756-Y board hooked up to a 286 micro-computer through an A/D converter. The balance was calibrated with a 100 mg weight measured with a Mettler AE 163 balance. The furnace thermocouple was calibrated to give the sample temperature. The calibration was performed by using the Curie point temperatures of three metals in the range of 163°C to 595°C.

Kinetic rate parameters were found by using a non-isothermal technique that uses data generated during a heat-up ramp. The technique is based on the following equation that relates the yield of volatiles, V , to the absolute temperature, T , heating rate, m , activation energy, E , frequency factor, A , and ultimate yield, V_{inf} :

$$V = V_{inf}[1 - \exp((-AT/m((e^{-E/RT}))/E/RT))]$$

The above equation can be transformed to the following relation that gives new coordinates to plot the data to find E and A.

$$-\ln\{(m/RT^2)(\ln(1/(1-V_{bar})))\} = E/RT - \ln A/E$$

where V_{bar} is V/V_{inf} [26].

To gain more confidence in the kinetic rate parameters obtained with the non-isothermal technique, data sets should be generated from several heating rates that vary at least an order of magnitude. Due to temperature limitations of our TGS-2, the dial heating rates of 0.31°C/min and 5°C/min were used. This corresponds to one order of magnitude rise in heating rate. To achieve higher orders, the kinetic rate parameters acquired from these data sets were used in a computer model of the particle temperature history in our radiant flow reactor with heating rates of approximately 10⁴K/sec. The results are promising and are fully described later.

In the TGS-2 experiments, 21 micron sized pyrite was used (American Minerals). The procedure consisted of taring out the weight of a platinum sample pan in an argon stream of flow rate 45 cc/min. The weighed pyrite sample was placed in the pan, the system was sealed, and the flow rate increased and then let to run for 30 minutes to purge out the air. For the dial heating rate setting of 5°C/min, the sample was heated to 600°C and left to soak at this temperature until the weight of the sample remained constant. For the 0.31°C/min setting, the sample was heated first to 440°C/min at 20°C/min, then to 600°C/min at 0.31°C/min. There was no weight loss up to 440°C/min so this did not affect the results for the lower heating rate.

In all the experiments, there was a slight decrease in the weight at about 525°C/min, followed by a continual drop in mass to 600°C/min. This is seen in Fig. 6.9, for the 5°C/min case. The initial drop in mass was believed to be an impurity and a correction was needed to account for this mass. The correction was determined from X-ray diffraction which identified which type of pyrrhotite was left as product. The scan of the pyrrhotite is seen in Fig. 6.10. The powder diffraction program MicroID from Materials Data, Inc. determined that the best match to the scan was pyrrhotite 11-T which has a molecular weight of 82.88 g/mol. This pyrrhotite corresponds to a yield of 24 wt%. Because the measured yield was 25 wt%, a 1 wt% correction was used. In addition, an offset correction of .3 wt% was subtracted from the TGS-2 data because of a shift in the baseline. The corrected data are plotted in Fig. 6.12 along with best fit lines from the following analysis.

Figure 6.9. % Original Weight Loss of Pyrite versus Temperature for a Dial Heating Rate of 5.0°C/min.

Figure 6.10. X-ray Scan of Pyrite Pyrolysis Product (40kV 20mA).

Before plotting the data on the new coordinates the heating rate was checked with a best fit line to the temperature history. It turned out that the actual setting was off the dial setting by about 16%. Fig. 6.11 shows the data plotted on the new coordinates and the line represents the linear regression fit to the data. An important feature of the plot is that both sets of data fall on a single line. This conclusively shows that the reaction is first order. If there had been a spread in the two sets of data, then a distributed activation energy model would have been used.

Modified Arrhenius Diagram

Figure 6.11. Modified Arrhenius Diagram for Two Heating Rates.

Fig. 6.12, a plot of the fractional yield during heat-up, was found using Professor Stephen Niksa's DAEMPLAT program that calculates the yields for a sample for any ramped temperature program and specified kinetic rate parameters. It should be noted that the lower heating rate was set at 4.39×10^{-3} K/sec because the program does not converge below this level. As seen in the plot, the values of 56.8 kcal/mol for the activation energy and 3.5×10^{11} /sec for the frequency factor give good fits to data generated from two heating rates that varied an order of magnitude.

Fractional Yield During Heatup

Figure 6.12. Fractional Yield During Heat-up.

The kinetic rate parameters found above were used in the PYRTEMP particle temperature program to determine if they could be applied to the high temperature rapid heating pyrolysis of pyrite particles. The gas yields predicted by the computer code was compared to those found from the radiant suspension flow reactor. Preliminary results with the code proved inconclusive because the residence times that it predicted were a factor of two higher than the experimental residence times. Since the particle temperature, which directly affects the gas yields, is proportional to the residence time, the code needed further modification to resolve this important problem.

Two different solutions to the problem achieved moderate success. One method, fully described in Chen [27], utilized the solution to a developing momentum boundary layer on a flat plate with a single experimentally found fitting parameter to calculate the velocity of the gas. The second method, from Sparrow [28], uses a linearized momentum equation to find the gas velocity. The results of the cold furnace residence time measurements and the calculations using the two methods are in Table 6.1. The first method, called BL-factor in the table, gives residence times which are in very good agreement with the measured

residence times. The Sparrow method gives residence times which are well above the measured for lower mean gas velocities. Both methods give the same percentage error in calculating the only successful hot furnace residence time measurement at 20 cm/sec.

Table 6.1. Measured and Calculated Residence Times

	Measured	BL - factor		Sparrow		
Vmean	Res Time	Res Time	%error	Res Time	%error	
(cm/sec)	(msec)	(msec)		(msec)		
	20	260.47	298.19	14.48	399.68	53.45
	30	240.27	189.07	-5.59	279.06	39.34
	40	179.35	170.55	-4.91	215.06	19.91
	50	167.60	165.30	-1.37	175.33	4.61
	60	147.80	147.58	-0.15	148.22	0.28
hot 20		143.00	122.79	-14.13	163.72	14.49

Although the BL-factor method was better at predicting the correct cold furnace residence time, it failed to achieve any discernable gas yields, as seen in Table 6.2. This can be explained by the fact that the maximum particle temperatures calculated were below 900 K, the approximate temperature when pyrite began to appreciably decompose in TGA experiments with the highest heating rate attainable. The Sparrow method, on the other hand gave higher particle temperatures and reasonable gas yields for three of the cases. Although the yields do not match those from experiment, the results indicate that the relatively high activation energy and frequency factor from the slow heating rate TGA experiments could be used for higher heating rates. Refinement of the code and the use of the correct pyrite emissivity will improve the accuracy of the yields and lend further support for the use of the kinetic parameters found.

Table 6.2. Measured and Calculated Gas Yields

	Measured	BL - factor		Sparrow	
Vmean	Yields	Yields	Max Temp	Yields	Max Temp
(cm/sec)	(by mass)	%	(K)	%	(K)
20	82.64	0.00	861.69	11.94	1145.23
30	61.04	0.00	824.76	0.98	1051.62
40	15.24	0.00	794.68	0.04	948.60
50	6.77	0.00	747.44	0.00	829.24
60	5.27	0.00	742.36	0.00	832.97

6.3 DISCUSSION

On the basis of thermodynamics, the observed yields are expected at temperatures of over 500 degrees lower than the reported furnace temperatures. Our experimental conditions are used as inputs to the computer code STANJANR, Ruben Diaz's modified version of STANJAN, which accounts for iron-bearing species. In STANJAN, the element potential method is utilized to calculate equilibrium compositions of chemical systems.

The calculated equilibrium compositions for the operating conditions in our inert pyrolysis studies are depicted in Fig. 6.13. Compared in Fig. 6.13 are the predicted and observed $\text{Fe}_{0.877}\text{S}$ yields for various temperatures. Conversion of FeS_2 to $\text{Fe}_{0.877}\text{S}$ is predicted to occur from 750K (5% conversion) to 800K (100% conversion).

Thermodynamic predictions are even less consistent for the oxidative study. From 600K to 650K, the calculated iron phase partition is 53% Fe_2O_3 and 47% FeS_2 . Between 650K and 800K, the computational procedure experiences singularities because of major phase changes in the chemical system. From 800K to 1300K, the iron is distributed between Fe_3O_4 and $\text{Fe}_{0.877}\text{S}$. In this temperature range, the $\text{Fe}_{0.877}\text{S}$ content declines from 56% to 48%. From 1300K to 1600K, the computations again become singular because of a phase change from $\text{Fe}_3\text{O}_4\text{-Fe}_{0.877}\text{S}$ to FeS-FeO .

Figure 6.13 Comparison of experimentally observed (solid curve) and calculated equilibrium (dotted curve) weight fraction of $\text{Fe}_{0.877}\text{S}$ at various wall temperatures. Conditions are inert pyrolysis, 3.9 slm Ar, 0.8g FeS_2 /min.

A scheme to monitor the transformation of pyrite in rapid pyrolysis has been demonstrated, and the XRD assignments of the condensed mineral phases with quenched samples seem especially promising. Nevertheless, these results depict the performance of the experimental systems more than the reaction dynamics. In the near future, the sequence of experiments and analyses illustrated here will be conducted for ranges of oxygen level and particle size. They will also be extended to various synthetic carbons with tightly classified pyrite inclusions.

APPENDIX A

FOULING AND SLAGGING

A1. INTRODUCTION

Much has been written about fouling and slagging, because it constitutes a major technological limitation on pulverized fuel firing. The primary journal articles on the topic are numerous, but no individual one contains enough information for someone unfamiliar with the subject. Review articles and books such as those by Reid [1] and Badin [2] are better introductions to the topic. In fact, unless otherwise indicated, the contents of this chapter are drawn from Badin's work.

Fouling and slagging refers to the deposition of mineral matter on steam tube walls during pulverized fuel firing. Each year, the costs associated with the almost 50 million tons (1975) [1] of mineral matter that passes through furnaces is estimated at \$500 million (1981) [2]. The ash deposits disrupt the heat flux and gas flow patterns as well as corrode the reactor walls. The disruption of heat flux patterns reduces heat transfer through furnace tube walls by up to 25%. The reduced heat transfer increases the temperature of the exit flue gas, leading to a high steam temperature from the superheater. The net effect is a reduction in performance, reliability, and efficiency.

The Keystone experience [1] illustrates the operational difficulties caused by ash deposition. The facility could not be operated at its capacity of 900MW due to the formation of slag deposits and their subsequent mechanical failure. To lower its temperature, the furnace was operated at 50% excess air. Nevertheless, the availability decreased because of fly ash erosion and an imbalance between superheater and reheater surfaces. Consequently, the operating levels had to be lowered to 740 MW and 780 MW in the two units.

A2. TYPES OF DEPOSITION

Fouling and slagging is a term that encompasses many different types of deposition. Badin describes four major groups of deposition in the order of their formation along the flow path of a coal-fired unit. They are slag, high-temperature fouling (with corrosion as a subgroup), low-temperature fouling, and low-temperature slag deposits.

Slag deposits are usually bonded on radiatively-heated furnace walls and other surfaces at temperatures between 1000C and 1650C. Slagging is initiated by a porous and loosely adherent deposition of fine (under 30 micron diameter) fly ash particles near their softening temperature. Subsequently, compounds of alkali and alkali-earth metals and iron are deposited at temperatures higher than the ash-softening temperature. This secondary deposition leads to a dense and adhesively bonded layer.

High-temperature fouling constitutes the second type of deposits. These deposits are formed between 550C and 1100C on convection-heated surfaces such as superheaters and reheaters. They are initiated by a white liquid layer of complex sulfates tightly bonded to steel walls. If the temperature is between 600C and 750C, the sulfate layer destroys the protective oxide layer on the steel walls, thereby initiating a corrosion deposit. Subsequent accumulation of flyash generally leads to the formation of a sintered layer.

Closer to the reactor outlet, the third type of deposits, low-temperature fouling, begins to form on cooled surfaces such as air heaters and economizers. These deposits are formed as the temperature of the exit flue stream dips below 150C, causing water and acid to condense.

In the same region of the reactor, low-temperature slag may form on slightly warmer surfaces. It is initiated by the formation of $\text{Na}_2\text{S}_2\text{O}_7$ from SO_2 , O_2 , and Na_2SO_4 at temperatures between 250C and 320C. The resulting low-temperature slag is more strongly bonded than its high-temperature counterpart.

A3. STICKY ALKALINITY

All four types of deposits stem from a common set of physico-chemical characteristics of mineral matter and reactor walls termed sticky alkalinity. These traits include depression of ash-softening temperature, low-melting eutectics, and fluxing actions.

In slagging, deposition may arise from the sticky alkaline features of either molten ash particles or sulfate-coated reactor surfaces. The sticky alkalinity of ash particles is attributed to compounds of basic ions such as Fe^{2+} , Ca^{2+} , and Mg^{2+} . These compounds act as fluxes that form low-melting silicates. Ordinarily, the concentration of these basic ions is low, relative to acidic ions. When the concentration of basic and acidic oxides become equal, however, the ash-softening temperature is lowered to a minimum. Even after the ash particles have become molten, the basic ions continue to enhance the particles' adhesion efficiency by reducing the melt viscosity.

On the other hand, with reactor surfaces, sticky alkalinity is promoted by surface oxidation and alkaline deposition. In this situation, sodium and iron compounds are strongly implicated, for enhancing adhesiveness.

In contrast with slagging, high-temperature fouling stems from sticky alkaline features of the vapor phase. Condensation of gaseous alkaline species is the postulated mechanism of sticky alkalinity. Furthermore, the selective condensation of these alkaline species is reported to occur at approximately 730C.

Despite their apparent differences, the various sticky alkaline traits can be empirically correlated in terms of a single parameter, B/A, the base-to-acid ratio of coal ash, defined as

$$B/A = \frac{\text{Fe}_2\text{O}_3 + \text{CaO} + \text{MgO} + \text{Na}_2\text{O} + \text{K}_2\text{O}}{\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{TiO}_2}$$

This parameter is used in the following slagging factor for non-western coal, $R_s = (B/A) \times (\%S \text{ in dry coal})$ as well as the fouling index, $R_f = (B/A) \times (\%\text{Na}_2\text{O in ash or deposit})$. Clearly, the higher the base-to-acid ratio, the greater the fouling and slagging.

A4. STICKY ALKALINE CHEMICAL REACTIONS

To a great extent, the various sticky alkaline features that lead to fouling and slagging are rooted in three fundamental types of chemical transformations. These transformations are acid-base reactions, reactions of alkali and alkali-earth compounds, and reactions of iron compounds. At any time, these reactions occur in different combinations that lead to deposit formation.

Appreciating the significance of acid-base reactions "involves thinking of the slag as a two-component system composed of acids and bases, and modified by alkali content to account for fouling" [2]. Acids are polymer formers or oxide ion acceptors, and bases are the opposite.

Acid-base reactions are important because they lower the ash-melting temperature. In reducing zones there is a reduced concentration of polymer-forming ions (acids). This reduction in acids promotes deposition by decreasing melt viscosity. Under these conditions, (at 60% CO and 40% CO₂), ash melting accelerates between 900C and 1000C, and is controlled by the iron-rich corner of the phase diagram of the acid-base system FeO(base)-Al₂O₃(acid)-SiO₂(acid). But under oxidizing conditions, other acid-base systems become important. The eutectic of the K₂O(base)-FeO(base)-SiO₂(acid) becomes dominant, as potassium is the most important fluxing agent (below 1100C). Above 1200C, calcium and iron become fluxing agents under these oxidizing conditions.

Another class of reactions implicated in deposits formation consists of high-temperature reactions involving alkaline and alkaline-earth compounds. The characteristics of these reactions are understood, for they have been thoroughly investigated. They are usually preceded by low temperature decomposition (eg. K₂O at 350C) and sublimation (eg. Na₂O at 1275C) reactions. As the temperature rises to between 1300K and 1500K, NaOH is formed through gas phase reactions involving H₂O. Sulfates are also formed from gas phase reactions, but these involve sulfides. When these reactions occur adjacent to iron-containing metal, complex sulfates such as Na₃Fe(SO₄)₃ are produced. Nevertheless, the bulk (over 75%) of the available sodium is involved in reactions that form Na₂SiO₅, when the temperature is between 1300K and 1850K.

The last important class of fouling and slagging reactions are those involving iron-bearing minerals. Iron is generally regarded as one of the greatest contributors to fouling. Under reducing conditions, iron pyrite acts as a fluxing agent that reduces the melting

temperature of the other impurities. Even after the ash has become molten, iron compounds increase its adhesion efficiency by decreasing its viscosity. In corrosion deposits, the associated sulfur in iron-bearing minerals is actually more important than the iron itself. The most corrosive substances between 590C and 760C are sulfates which may not contain iron. Furthermore, free SO_3 can sulfidize and oxidize the reactor's steel walls.

A5. REACTIONS OF IRON-BEARING MINERALS

The central role of iron and sulfur compounds in deposition makes pyrite (FeS_2) a very significant mineral impurity. Its significance is increased by its preponderance. Pyrite and iron are typically the third most abundant impurity mineral and element in U.S. bituminous coal. Usually, about half of the Fe_2O_3 found in ash originates from pyrite [1]. During combustion, the pyrite transforms into a series of sticky alkaline derivatives before terminating as an iron oxide.

Some of these pyrite derivatives contribute more effectively to deposition than others. Traditionally, Fe_2O_3 is identified as the initiator of fouling and slagging, because it is often reported as the dominant phase in the innermost layer of slag deposits. Traditional analyses fail, however, to distinguish the different iron phases. Furthermore, any detected Fe_2O_3 could be the oxidation product of deposits of other iron compounds (as Fe_2O_3 is rarely found in the exit flue gas).

Alkalinity considerations and the increase of deposition under reducing conditions also make it unlikely that Fe_2O_3 initiates deposition. Fe_2O_3 is an Fe^{3+} compound formed under oxidizing conditions. It is actually Fe^{2+} compounds formed under reducing conditions which act as low-temperature fluxing agents to form low-melting complex silicates [21]. The oxides among these Fe^{2+} compounds also enhance the stickiness of molten ash by decreasing its viscosity. For instance, FeO forms the low-melting Fe_2SiO_4 , which, along with FeS , forms a low-melting eutectic anticipated to initiate the deposition. Once slagging has begun, FeS may form another low-melting silicon oxide, FeSiO_3 , to accelerate it.

Direct comparisons also confirm that Fe^{2+} compounds such as FeO , FeS , and FeS_2

deposit more effectively than Fe_2O_3 . Many studies establish that FeO lowers the ash-fusion temperature much more than Fe_2O_3 . Abbott and Austin [4] show that even FeS_2 (although it first transforms to Fe_{1-x}S) deposits more effectively than Fe_2O_3 . FeS_2 pellets wet the steel substrate surface with a contact angle that is 30 degrees lower, stick at temperatures that are 200C lower, and adhere 5 times as strongly as Fe_2O_3 pellets.

Because the deposition efficiency of FeS_2 derivatives vary, it becomes important to characterize the reactions that determine how much time is spent in each phase. These reactions are well-characterized at temperatures of under approximately 1000K, and their products are known to be influenced by the oxygen level. Under highly oxidizing conditions, Fe^{3+} compounds such as Fe_2O_3 are favored, whereas under reducing conditions, Fe^{2+} compounds such as FeO and FeS are predominant.

Below 750C and in excess air, pyrite is converted to Fe^{3+} compounds. When oxidized in air at 400C to 500C, FeS_2 is often reported to form SO_2 , Fe_2O_3 , and $\text{Fe}_2(\text{SO}_4)_3$. The air oxidation of Indian pyrite [2], monitored with Mossbauer spectroscopy, reveals that the sulfates are formed first, and from these sulfates, the Fe_2O_3 is formed. The sulfate continues to oxidize until its content decreases to 9%, according to gravimetric calculations from thermogravimetric combustion.

Other low-temperature oxidation studies [2] do not report the sulfate intermediates, however. Thermogravimetry at 600K to 900K of extraneous pyrite as well as inclusions exhibit two distinct stages. The first is desulfurization to FeS , which occurs at the same rate as coal combustion. The second is oxidation of the FeS , at a much lower rate than coal combustion. Other studies [2] confirm that the FeS is oxidized to Fe_3O_4 and SO_2 at 500C. The overall conversion of pyrite to Fe_2O_3 in O_2 at 400C, increases from 7% to 100% when the pyrite is encased in coal, based on Mossbauer spectroscopy.

Under reducing conditions, FeS_2 forms a partial FeS melt at 282C, and this melt becomes increasingly richer in FeS until all the FeS_2 is converted by 600C. Before the temperature reaches 600C, liberated sulfur can migrate through the melt and sulfidize tube surfaces. If the temperature is increased even higher, to between 540C and 1000C, the combustion of the coal matrix induces local reducing conditions regardless of the initial conditions. This causes a shift from Fe^{3+} to Fe^{2+} compounds. Consequently, in coal-fired units, 80% of the iron occurs as Fe^{2+} , and the predominant iron compound is FeO .

The formation of local reducing zones with increasing temperature makes the dearth of high-temperature iron studies even more significant. The few studies that exist

have been synthesized into a kinetics model [3]. These studies suggest that FeS_2 transforms according to the following sequence: FeS_2 , Fe_{1-x}S , Fe-S-O , Fe_3O_4 , and at low temperatures and high oxygen levels, Fe_2O_3 . Further work, is however, necessary to determine the invariance and the associated kinetics of this sequence of transformations.

REFERENCES

1. Reid, W. T., "Coal Ash - Its Effect on Combustion Systems," Chemistry of Coal Utilization, Second Supplementary Volume (Ed. Martin A. Elliott), John Wiley & Sons, Inc., New York. 1981.
2. Badin, E. J., *Coal Combustion Chemistry - Correlation Aspects*, Elsevier Science Publishers B.V., Amsterdam, 1984.
3. Srinivasachar, S. and Boni, A., *Fuel* 1989, **68**, 829.
4. Abbott, M. F. and Austin, L. G., *Fuel* 1982, **61**, 765.
5. Jorgensen, F. R. A., *Trans. Inst. Min. Metall. Sect. C*, 1981, **90**, 1.
6. Asaki, Z., Mori, S., Ikeda, M., and Kondo, Y., *Met. Trans. B* 1985, **16B**, 627.
7. Huffman, G. P., Huggins, F. E., Levasseur, A. A., Chow, O., Srinivaschar, S., and Mehta, A. K., *Fuel* 1989, **68**, 486.
8. Hoornstra, J. and Dunn-Rankin, D., "Size Distribution Characteristics of Size-Graded Pulverized Coal," 1987 International Conference on Coal Science (Eds. Moulijn, J. A., Nater, K. A., and Chermin, H. A. G.), Amsterdam.
9. Senior, C. L., "Submicron Aerosol Formation During Combustion of Pulverized Coal," Ph.D. Thesis, California Institute of Technology, 1984.
10. Levendis, Y. A. and Flagan, R. C., *Combust. Sci. and Tech.* 1987, **53**, 117.
11. Jorgensen, F. R. A., *Trans. Inst. Min. Metall. Sect. C*, 1981, **90**, 10.
12. Huffman, G. P., Huggins, F. E., and Dunmyre, G. R., *Fuel* 1981, **60**, 585.
13. Pike, S., Dewison, M., and Spears, A., *Fuel* 1989, **68**, 664.
14. Klug, H. P. and Alexander, L. E., *X-Ray Diffraction Procedures for Polycrystalline and Amorphous Materials*, John Wiley & Sons, Inc., New York, 1954.
15. Cullity, B. D., *Elements of X-Ray Diffraction*, Addison-Wesley Publishing Company, Inc., USA, 1978.
16. Chen, J. and Niksa, S., Paper No. 89-11, WSS/CI Spring Mtg., Pullman, WA, March 1989.
17. Chen, J. and Niksa, S., "Paper No. 89-75, WSS/CI Fall Mtg., Livermore, CA, October 1989.
18. Marlow, D., "An Experimental Study of the Pyrolysis and Combustion of the Volatiles from Coal," Unpublished Report, Stanford University, 1990.
19. Astle, M. J. and Weast, R. C., Eds., *CRC Handbook of Chemistry and Physics, 60th Edition*, CRC Press, Inc., Boca Raton, Florida, 1980.

20. Groves, S. J., Williamson, J., and Sanyal, A., *Fuel* 1987, **66**, 461.
21. Ely, F. G. and Barnhart, D. H., "Coal Ash -- Its Effect on Boiler Availability," Chemistry of Coal Utilization, Supplementary Volume (Ed. Lowry, H. H.), John Wiley and Sons, Inc., New York, 1963.
22. Lau, C. W., HTGL Memorandum Report 2-90, Mechanical Engineering Department, Stanford University, August 1990.
23. Schwab, G. and Philinis, J., *J. Am. Chem. Soc.* 1947, **69**, 2588.
24. Reynolds, W. C., "The Element Potential Method for Chemical Equilibrium Analysis: Implementation in the Interactive Program STANJAN, Version 3," Mechanical Engineering Department, Stanford University, 1986.
25. Kulerud, G. (1967) Sulfide Studies, in P. H. Abelson (ed.), *Researches in Geochemistry*, John Wiley and Sons, New York, p. 288.
26. Niksa, S., Heyd, L. E., Russel, W. G., and Saville, D. A. *Twentieth Symposium (International) on Combustion*, The Combustion Institute, 1985, p. 1445.
27. Chen, J. (1991) Ph.D. Dissertation Thesis, Mechanical Engineering Department, Stanford University.
28. Sparrow, E. M. et al., *Phys. Fluids* 7, 338 (1964).

END

**DATE
FILMED**

4 / 14 / 92