Coal Plasticity at High Heating Rates and Temperatures

RECEIVED

MAR 02 1993

Tenth Technical Progress Report

Third Quarter: July 1 1992-September 30 1992

OSTI

Sarakorn Gerjarusak, William A. Peters, and Jack B. Howard

Energy Laboratory and Department of Chemical Engineering
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government, nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trade mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Submitted to the United States Department of Energy
Pittsburgh Energy Technology Center
Attention: Dr. Philip M. Goldberg

PREPARED FOR THE UNITED STATES DEPARTMENT OF ENERGY
Under Contract No. DE-FG22-89PC-89773
Date Submitted: November 1992

"US/DOE Patent Clearance is not required prior to the publication of this document."

Abstract

Effects of coal type on coal plasticity are investigated. Seven coals, from the Argonne premium sample bank ranging from lignite to low volatile bituminous, are studied. Different indices and structural data of a coal are shown to affect its plastic behavior. A coal-specific parameter incorporating the effects of labile bridges, oxygen, and hydrogen on plasticity has been used to successfully correlate measured values of maximum plasticity (i.e. minimum apparent viscosity) at elevated temperature with coal type.

Introduction

A high temperature plastometer with a new cone-shaped shearing disk is being used to measure the apparent viscosity of molten coals as affected by pressure (vacuum-10 atm He), heating rate (200-800 K/s), holding temperature (900-1100 K), and coal type. Seven coals, from the Argonne National Laboratory premium coal sample bank, are being studied: Beulah-Zap lignite (ND), Wyodak subbituminous (WY), Illinois No. 6 hvb (IL), Pittsburgh No. 8 hvb (PT), Lewiston-Stockton hvb (WV), Upper Freeport mvb (UF), and Pocahontas No. 3 lvb (PO). In this study, all hvb, mvb, and lvb coals show very good plastic behavior, but as would be expected the lower rank ND and WY coals did not exhibit any plasticity. For the plastic coals, relationships between simple indices of coal type and observed plasticity need to be established. From the present data, there is no evidence for a continuous increase (or decrease) in plasticity with increasing coal rank. This report will concentrate on the investigation of the relationships between maximum plasticity (and thus maximum metaplast concentration) and simple indices of coal type for different coals.

Different Indices of Coal Type

The simplest indices of coal type for different coals are their elemental contents. Coal is generally made up of C, O, H, N, S, and mineral matter. In general, as the rank increases, the carbon content

of a coal increases, while its oxygen content decreases. The balance of the mass consists mainly of hydrogen and, in high sulfur coals such as Illinois No. 6 hvb, organic sulfur. Carbon and hydrogen NMR studies also allow for more refined classifications of coal elements such as fraction of aromatic carbon (carbon aromaticity, C_{fa}) and fraction of hydrogen attached to aromatic carbon (proton aromaticity, H_{fa}). The ultimate analysis and structural data of the coals studied here are shown in Table 1.

A plot of maximum plasticity vs. %C for different coals is shown in Figure 1. Hvb coals are shown to be very plastic. Although mvb and lvb coals are less plastic than hvb coals, they still exhibit a strong plastic behavior. However, the %C content does not correlate well with plasticity.

Labile Bridges

Labile bridges are mostly aliphatic, with some alicyclic and heteroatomic functionalities. They are the bridges which link the larger aromatic clusters or molecules together. The initial fraction of labile bridges are important since they are the key reaction centers. When a labile bridge is heated, it either dissociates to release smaller aromatic fragments or condenses to form a char linkage and release noncondensable gases (Niksa and Kerstein, 1991). Scissions of labile bridges can therefore create smaller aromatic molecules or liquid metaplast. Thus, coals with higher fractions of labile bridges should exhibit greater plasticity. Figure 2 shows a plot of maximum

TABLE 1: Ultimate Analysis, Structural, and Plasticity Data for Argonne Premium Coals

	ND lig	WY sub	IL hvb	PT hvb	WV hvb	UFm vb	PO l vb
%C dmmf ^a	74.05	-76.04	80.73	84.95	85.47	88.08	91.81
%O dmmf ^a	19.13	16.90	10.11	6.90	6.68	4.72	1.66
%H dmmf ^a	4.90	5.42	5.20	5.43	5.44	4.84	4.48
Carbon Aromaticity ^b , C _f _a	0.57	0.60	0.67	0.74	0.75	0.80	0.88
Proton Aromaticity ^c , H _f _a	0.24	0.27	0.30	0.35	0.36	0.39	0.45
Max Plasticity (Pa•s) ^d , vacuum	n/a	n/a	2690	2500	2550	5019	7455
Max Plasticity (Pa•s) ^d , 1 atm He	n/a	n/a	1758	1286	1694	2583	5337

a: Vorres, 1989

b: Ko, 1988

c: Niksa, 1991

d: Gerjarusak, 1992

IL: Illinois No. 6 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 1: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. %C dmmf.

Maximum Plasticity vs. %C

IL: Illinois No. 5 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 2: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. fraction of aliphatic carbon content, 1-Cfa.

Maximum Plasticity vs. Aliphatic Carbon Fraction

plasticity vs. fraction of aliphatic carbon content ($1-C_{fa}$). In general, hvb coals with higher aliphatic carbon fraction (and thus higher labile bridge fractions) exhibit greater plasticity than mvb and lvb coals with lower aliphatic carbon fraction.

Oxygen Content

Oxygen also plays an important role in coal devolatilization. Oxygen promotes cross-linking of labile bridges which suppresses formation of liquid fragments or metaplast (Niksa and Kerstein, 1991). Coals with higher oxygen content might therefore be expected to exhibit lower plasticity, especially since the main volatile products of their pyrolysis are noncondensable gases. Figure 3 shows a plot of maximum plasticity vs. %O content of a coal. Here, hvb coals with higher oxygen content still exhibit significant plasticity, more than mvb and lvb coals with lower oxygen content.

Hydrogen Content

Finally, hydrogen is important in its role in stabilizing radicals. The abstractable hydrogen is hydrogen which is not attached to aromatic carbons. Its inventory depends on H_{fa} and the total amount of hydrogen in the parent coal. Abstractable hydrogen stabilizes aromatic molecules, and is thus believed to promote plasticity. Coals with higher hydrogen content would therefore be expected to exhibit higher plasticity (Ko et al., 1988 and Niksa, 1991). Figure 4 shows a plot of maximum plasticity vs. %H content. In general, hvb coals with

IL: Illinois No. 6 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 3: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. %O dmmf.

Maximum Plasticity vs. %O

IL: Illinois No. 6 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 4: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. %H dmmf.

Maximum Plasticity vs. %H

higher hydrogen content exhibit greater plasticity, i.e. lower apparent viscosity, than mvb and lvb coals with lower hydrogen content.

Formulation of A Parameter to Correlate Plasticity with Coal-type

Ko (1988) and Ko et al. (1989) correlated maximum tar yield in rapid pyrolysis of powdered coal (diameter < 100 μm) with a coal-type parameter X_{tar} :

$$X_{\text{tar}} = \frac{(\text{no. of labile bridges})(\text{amt. of abstractable H})}{(\text{no. of cross-linked bridges})} \quad 1)$$

from the assumption of that tar generation proceeds via the global mechanism:

Here, the importance of labile bridges, oxygen, and hydrogen is recognized in determining each of the three factors used to determine X_{tar} . The number of labile bridges is assumed to be proportional to the aliphatic carbon content of the raw coal. The amount of the abstractable hydrogen is assumed to be proportional to the amount of elemental carbon in the raw coal. The number of cross-linked bridges is assumed to be proportional to amount of the elemental oxygen and organic sulfur in the raw coal. Ko's analysis provided a good linear correlation between maximum tar yield at various pressures and X_{tar} . (Ko, 1988 and Ko et al., 1989)

In light of Ko's previous correlation and the strong relationship between metaplast and tar, it seems plausible to try to correlate plasticity with a coal-type parameter. This coal-type parameter should incorporate the importance of labile bridges, oxygen, and hydrogen content. First, the coal-type parameter for plasticity is formulated as:

$$X_P = \frac{(\text{no. of labile bridges})(\text{amount of hydrogen})}{(\text{amount of oxygen})} \quad 3)$$

with:

$$\text{no. of labile bridges} = ((1-C_{fa}) \cdot [C \text{ wt\% dmmf}])^{1.8} \quad 5)$$

taken from Ko's Xtar formulation (Ko, 1988) and:

$$\text{amount of hydrogen} = [H \text{ wt\% dmmf}]/1.0079 \quad 6)$$

$$\text{amount of oxygen} = [O \text{ wt\% dmmf}]/15.994 \quad 7)$$

A plot of maximum plasticity vs. X_P is shown in Figure 5. A linear correlation between plasticity and X_P is quite good at vacuum and better at 1 atm He pressure. However, knowing that not all hydrogen participates in stabilizing free radicals, it seems logical to replace the amount of hydrogen in equation 3 by the amount of abstractable hydrogen. Here, the amount of abstractable hydrogen is formulated as the amount of hydrogen which is attached only to

IL: Illinois No. 6 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 5: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. coal-type parameter, X_p .

Maximum Plasticity vs. Xp

aliphatic carbon atoms minus a correction suggested by Ko (1988) to account for experimental observations that OH groups may compete for the abstractable hydrogen:

$$\begin{aligned} \text{amount of abs hydrogen} = & (1-Hf_a) \cdot [\text{H wt\% dmmf}] / 1.0079 \\ & - [\text{OH wt\% dmmf}] / 17.002 \quad 8) \end{aligned}$$

Ko (1988) assumed that abstractable hydrogen should be proportional to aliphatic hydrogen. In formulating a relation for estimating abstractable hydrogen from coal elemental composition, he assumed that aliphatic hydrogen concentration in the coal was proportional to total hydrogen concentration in the coal. For the present investigation, data are available on the actual fraction of aromatic hydrogen in the coals of interest. Therefore we can directly calculate the fraction of aliphatic hydrogen as $1-Hf_a$.

A plot of maximum plasticity vs. a revised X_p corrected to better account for the abstractable hydrogen ($X_p(\text{corrected})$) is shown in Figure 6. The linear fit between maximum plasticity and $X_p(\text{corrected})$ is better than that of the uncorrected X_p , especially in correlating data under vacuum.

Discussion

The present correlations represent an attempt to explain coal-type effects on coal plasticity. Here it has proved fruitful to formulate a coal-type parameter analogous to one proposed and utilized by Ko

IL: Illinois No. 6 hvb
PT: Pittsburgh No. 8 hvb
WV: Lewiston-Stockton hvb
UF: Upper Freeport mvb
PO: Pocahontas No. 3 lvb

Figure 6: Maximum Plasticity (minimum viscosity), MF, in vacuum and 1 atm He vs. coal-type parameter with abstractable hydrogen correction, $X_p(\text{corrected})$.

Maximum Plasticity vs, Xp(corrected)

(1988) to explain coal-type effects on coal plasticity. The effects of labile bridges, oxygen, and hydrogen in the specific coal are incorporated into the coal type parameter to explain their effects and hence the effects of coal type on coal plasticity. Although rich in labile bridges and hydrogen, lignites and subbituminous coals have abundant oxygen which promotes cross-linking. The formation of liquid fragments or metaplast is suppressed, leading to a lack of plastic behavior in these coals. The primary volatile products of their pyrolysis are low molecular weight gases. With much lower oxygen content than that of low rank coals, Hvb coals are also rich in labile bridges and hydrogen which leads to very good plastic behavior. High rank coals have lower plasticity than hvb coals because of they have considerably less labile bridges.

The coal-type parameter for correlating plasticity developed here is intended to be used as a rough guide in estimating the maximum plasticity, i.e. minimum apparent viscosity for a coal when experimental data are not available on the plasticity of that coal. One can calculate this parameter from knowledge of the elemental carbon, hydrogen, and oxygen contents of a given coal together with knowledge of its aromatic carbon, aromatic hydrogen, and hydroxyl group contents.

Future Work

A multiple independent parallel reaction (MIPR) kinetics model will be used to predict the magnitude and duration of plasticity of

different coals. The kinetics parameters of the MIPR model will be fitted from the available data using a nonlinear regression program.

Literature Reference

Fong, W. S., "Plasticity and Agglomeration in Coal Pyrolysis, " Sc.D. Thesis, Department of Chemical Engineering, MIT, Cambridge, MA, 1986.

Gerjarusak, S., W. A. Peters, and J. B. Howard, "Coal Plasticity at High Heating Rates and Temperatures: Ninth Technical Report to the U.S. Department of Energy," U.S. DOE Pittsburgh Technology Center, Contract No. DE-FG22-89PC-89733, September 1992

Ko, G. H., D. M. Sanchez, W. A. Peters, and J. B. Howard, "Correlations for Effects of Coal Type and Pressure on Tar Yields from Rapid Devolatilization," Twenty-Second Symposium (International) on Combustion, pp. 115-124, the Combustion Institute, Pittsburgh, PA 1989.

Ko, G. H., "Pyrolysis of Different Coal Types," Ph.D Thesis, Department of Chemical Engineering, MIT, Cambridge, MA, 1988.

Niksa, S. and Kerstein, A. R., "FLASHCHAIN Theory for Rapid Coal Devolatilization Kinetics. 1. Formulation," Energy and Fuels, 5, p. 647, 1991.

Niksa, S. , "FLASHCHAIN Theory for Rapid Coal Devolatilization Kinetics. 3. Modeling the Behavior of Various Coals," Energy and Fuel, 5, p. 665, 1991.

Vorres, K. S., Users Handbook for the Argonne Premium Coal Sample Program, U.S. Department of Energy, October 1989.

END

**DATE
FILMED**

3 / 17 / 93