ARGONNE NATIONAL LABORATORY
9700 South Cass Avenue, Argonne, Illinois 60439

ANL/MCT/RP--77582

DE93 004228

Materials and Components Technology Division

Research Summary — 1992

R. W. Weeks, Division Director

W. J. Shack, Associate Division Director

R. A. Valentin, Associate Division Director

Administration:

B. K. Baudino

W. E. Brewer

J. L. Donahue

W. H. Livernash

B. H. Malak

C. A. Malefyt

A. C. Smith, Jr.

D. L. Telfer

MASTER

November 1992

Contents

Overview of the Materials and Components Technology Division.....	1
Materials Technology	5
Ceramics	7
Corrosion.....	31
Mechanics of Materials	52
Tribology.....	66
Irradiation Performance.....	77
Components Technology.....	83
Superconductivity Applications.....	85
Analytical Thermal-Hydraulics.....	93
Thermal and Mechanical Sciences.....	103
Instrumentation and Nondestructive Evaluation.....	112
Transportation of Hazardous Materials	129
APPENDIX A: Regular MCT Employees.....	143
APPENDIX B: Honors, Awards, and Professional Activities.....	147
Program Index.....	157

Materials and Components Technology Division

Overview of the Materials and Components Technology Division

The Materials and Components Technology Division (MCT) provides a research and development capability for the design, fabrication, and testing of high-reliability materials, components, and instrumentation. Current divisional programs related to nuclear energy support the development of the Integral Fast Reactor (IFR); life extension and accident analyses for light water reactors (LWRs); fuels development for research and test reactors; fusion reactor first-wall and blanket technology; and safe shipment of hazardous materials. MCT Conservation and Renewables programs include major efforts in high-temperature superconductivity, tribology, nondestructive evaluation (NDE), and thermal sciences. Fossil Energy Programs in MCT include materials development, NDE technology, and instrumentation design. The division also has a complementary instrumentation effort in support of Arms Control Technology.

The MCT Division has approximately 120 regular employees, supplemented annually by more than 150 temporary employees (including visiting faculty members, postdoctoral appointees, graduate and undergraduate students, special term appointees, and visiting industrial personnel on collaborative program assignments). The Division is organized into 10 sections, as shown in the adjacent organization chart; a current listing of regular employees appears in Appendix A. Recent honors, awards, and professional activities of staff members are listed in Appendix B.

As shown in the graph below, financial support for MCT programs comes primarily from the Nuclear, Conservation and Renewables, Fossil, and Fusion offices of the U.S. Department of Energy (DOE), and from the U.S. Nuclear Regulatory Commission (NRC). Additional efforts are funded by the U.S. Department of Defense, the National Park Service, private industry, public utilities, the National Science Foundation, and the DOE Office of Basic Energy Sciences. Total funding for the Division in FY 1992 was approximately \$26 million.

The increased requirements regarding environment, safety, and health (ESH) issues mentioned in the previous edition of this report (1991) have been incorporated into standard operating procedures during the past year. In addition, in response to revised DOE policies, special attention has been given this year to "Conduct of Operations" and Quality Assurance in all our activities.

Ongoing MCT programs are summarized below; more detailed discussions are included in the Section reports that follow. Because several sections usually participate in each program area, an index by program area is included at the end of this book.

MCT Funding Sources for FY 1992

Fission Reactors

MCT is part of a multidivisional effort at ANL to develop the IFR concept that will be demonstrated at ANL's EBR-II reactor site in Idaho. MCT is involved in fuel development efforts that include computer modeling of fuel element performance, fuel behavior testing under normal and off-normal reactor conditions, and in-pile testing of IFR fuel elements. Plant life extension for commercial LWRs encompasses several issues related to materials and components. MCT is investigating phenomena such as stress corrosion cracking, environmentally enhanced fatigue, erosion and corrosion, embrittlement, flow distributions and flow-induced vibrations, together with modeling of fission-product behavior under accident conditions and component failure analyses (including Three Mile Island Unit 2 components), that will have significant effects on plant life extension. Efforts are also underway to evaluate new reactor designs for both commercial and research applications.

Fusion Reactors

The Division participates in design studies for magnetic-confinement fusion reactors through thermomechanical analyses of reactor components, and through materials testing. The latter includes vanadium alloy development with studies of radiation effects and compatibility with lithium or water, together with determination of tritium-release kinetics from solid breeder materials.

Transportation of Hazardous Materials

The Department of Energy is responsible for numerous shipments of nuclear and other potentially hazardous materials by all types of transport. To ensure the safe handling of these materials, detailed Safety Analysis Reports for Packaging (SARPs) are required. MCT reviews these reports technically and recommends whether Certificates of Compliance should be issued. This work is coordinated with the NRC and the U.S. Department of Transportation. The Division also conducts workshops to inform applicants of requirements, and it produces films and educational videotapes for both professional and general audiences about the procedures used to ensure safe transport of hazardous materials.

Conservation and Renewables

Fabrication of optimized conductors made from high-temperature superconducting (HTSC) materials continues to be a major research area for MCT, along with device development for early commercialization of high-temperature superconductivity. Bulk and thin- and thick-film configurations are all included in the program, which is carried out in close cooperation with industry, and a variety of high-temperature superconducting materials are employed. The Division is also responsible for the ANL Superconductivity Pilot Center, which supports joint work with industry to develop early applications of this technology. Contracts with more than 30 different companies have been negotiated. Ongoing efforts include work on optimized conductors, magnetic bearings, current leads,

and superconducting motors. An HTSC Processing Center is also operated by the Ceramics Section to train students and visiting faculty to work with these new materials; about 50 students work in the Center each year.

The DOE National Tribology Program is managed by the Tribology Section in MCT. This program, which is carried out cooperatively at a variety of industrial, government, and university laboratories, is aimed at developing enabling friction, wear, and lubrication technology for the transportation industry. Our development work covers materials that exhibit low friction and wear properties, synthetic lubricants to extend the temperature range of liquid lubricants, vapor-phase delivery systems, and coating technology for very-high-temperature solid lubricant applications. Tribological data bases for use by industry have been developed under the auspices of the national program. MCT carries out in-house tribology research to develop low-friction, wear-resistant surfaces and coatings by a variety of processes, including diamond film technology. New concepts are tested in the Division's tribological testing laboratory, and the laboratory tests are supplemented by instrumented engine testing.

State-of-the-art NDE techniques are being developed to improve the fabrication technology for ceramic and composite materials and to determine the integrity of components made from these materials. These NDE techniques include nuclear magnetic resonance imaging for density distributions, as well as microfocus X-rays for defect identification. The Intense Pulsed Neutron Source at ANL is used for residual stress analyses, and thermal wave imaging is under development for determining the reliability of coatings.

To reduce the use of refrigerants that are destructive to the ozone layer or that contribute to the "greenhouse" effect, small heat exchangers are under development to replace larger, less efficient ones. This requires new design correlations for pressure drop and heat transfer, and these are being developed in the Thermal and Mechanical Sciences Section. Improved heat transfer is also the goal of a program that is investigating friction-reducing fluid additives and phase-change slurries.

A joint venture with industry is underway to develop a predictive model for mold filling and solidification of metal castings. The resulting computer program will operate on an engineering workstation and should allow improved mold design in less time than is required with current empirical techniques.

Additional conservation efforts include a cooperative program with industry for developing improved refractories for steelmaking.

Fossil Energy

The MCT Division carries out a variety of base-technology and end-use-specific work in support of fossil energy systems. The supporting base technology includes development of structural ceramics and composites with improved fracture toughness, NDE techniques to evaluate these materials, sulfidation-resistant alloys and coatings, and advanced instrumentation for process control. End-use-specific work includes joint projects with

industry on the development of solid-oxide fuel cells (in cooperation with ANL's Chemical Technology Division), alloy testing and selection for advanced coal conversion systems, and acid rain effects on materials.

Other

The Division conducts basic studies on flow-induced vibrations, as well as cooperative materials work (with the Materials Science Division) in pursuit of a basic understanding of high-temperature superconductors. In addition, MCT has several instrumentation projects aimed at developing arms control technology.

Materials Technology

Ceramics

Section Manager: R. B. Poeppel

Principal Investigators: U. Balachandran, S. E. Dorris, K. C. Goretta, M. T. Lanagan,

P. S. Maiya, D. Singh, J. P. Singh, C. A. Youngdahl

Support Staff: J. T. Dusek,¹ J. J. Picciolo, A. Wagh¹

Technicians: J. E. Emerson, R. L. McDaniel

Postdoctoral Appointee: Jose Pullockaran

Secretary: S. M. Hagamann²

Students: A. Biondo,³ T. Brent,⁴ N. Browning,⁵ C.-J. Chen,³ J. Dawley,⁴ Y. Fang,⁶ A. Iyer,³

J. Joo,³ D. Kaufman,⁶ K. S. Kirkpatrick,⁷ S. Morissette,⁸ C. Murphy,⁹ B. C. Prorok,⁶

G. Risch,⁵ N. Vasanthamohan,³ M. Weber,⁷ M. Wheeler,¹⁰ C.-T. Wu,³ S. Zentack,¹⁰

W. Zhong³

Student Aide: Elissa Nichols

The central theme common to programs in the Ceramics Section is the application of ceramics to various energy systems. Emphasis of the work is on synthesis fabrication and characterization. Occasionally, projects are limited to selection and/or testing. Much of the work is ongoing since the previous Division Review in 1991. High-temperature superconductivity remains as our largest effort, and several new Superconductivity Pilot Center projects were initiated. Work in structural ceramics and composites, fuel cells, and actinide recycle continue, while the sodium heat engine program was brought to conclusion. New efforts in nuclear waste isolation and CO₂ utilization have been initiated. The small Work for Others project with Amoco on ceramic membranes for the oxidative coupling of methane has significantly expanded to include other gas-to-liquid fuel technologies, and a CRADA with funding from DOE Office of Fossil Energy was written. Another small Work for Others project, with Magneco/Metrel on refractories for steelmaking, has now expanded into another CRADA with funding from the DOE Office of Energy Research.

Additions have been made to the experimental capabilities of the section. A new JEOL Model 5400 scanning electron microscope was purchased. Recently, we have been able to achieve 200,000x magnification on ceramic samples. A Noran EDAX provides energy-dispersive X-ray analysis with a compositional sensitivity of ± 1 at.%. A Cryomagnetics, Inc., 7-T superconductive magnet was obtained and is being used to facilitate electrical characterization of high-temperature superconductors. It is equipped with a heater in the specimen chamber so that samples may be tested over a range of temperatures from 4.2 to

¹Special Term Appointee.

²Serves two sections.

³Illinois Institute of Technology.

⁴Purdue University.

⁵University of Cincinnati.

⁶University of Illinois at Chicago.

⁷Northwestern University.

⁸DePaul University.

⁹Memphis State University.

¹⁰Virginia Polytechnic Institute.

300 K (liquid-helium to room temperature). A 1000-A pulsed-current source has been constructed and instrumented for critical current tests. A universal extrusion machine was purchased for extrusion and coextrusion of superconducting wires. A universal testing system (Instron Model 4505) has been purchased and installed; this computerized system is routinely used for mechanical evaluation of ceramics and composites.

We have nearly completed an effort to generate written instructions for the safe operation of every piece of equipment. Equipment logbooks are maintained and include safety instructions, a listing of those authorized to use the equipment, and a record of the actual use. We have identified needed QES&H safety training, and most Section members have nearly completed all training requirements.

High-Temperature Ceramic Superconductors

The main goal of this work is to develop a high-temperature superconducting wire that will have practical applications. Generally, this translates to the specification that the material remains in the superconducting state over long lengths under the simultaneous conditions of temperatures >35 K and electric current density $>10^4$ A/cm² in magnetic fields >2 T. The three basic classes of material under intensive development are (a) the YBa₂Cu₃O₇ system, or 123, in which Y can be replaced by almost any rare earth element or by combinations of rare earths, any of which have a critical temperature (T_c) of ≈ 93 K; (b) the bismuth-strontium-calcium-copper oxide system, including those formulations in which some of the bismuth is replaced by lead; and (c) the thallium-barium-strontium-calcium-copper oxide system. In the thallium system, particular emphasis is being placed on the development of the so-called 1223 composition.

The dominant mechanisms that limit current density vary from one system to the other. In the YBCO system, the phenomenon of "weak-link" behavior—the difficulty encountered by supercurrents in traversing grain boundaries in bulk, polycrystalline material—limits the current density. This problem is overcome in the bismuth system by a textured microstructure in which the copper oxide planes are aligned with the direction of current flow. In the bismuth-based system, current density is limited by motion of the magnetic flux.

Still, progress since the previous review has been good. The Section has maintained its worldwide recognition as a leader. Recently, a 1000-A, 1-m-long conductor assembly was fabricated from YBCO for the Tokyo Electric Power Company to demonstrate the feasibility of using high- T_c material in underground electric power distribution. In bismuth conductors made by powder-in-tube technology, current densities of 10^5 A/cm² have been achieved at low temperature (in liquid helium), and 3×10^4 A/cm² is available at liquid nitrogen temperature.

Interest in the thallium 1223 system is based on the fact that magnetic flux may be pinned more easily in this system than in the bismuth system, together with the thought that similar textured microstructures can be developed.

Structural Ceramics and Composites

Initiation of a fracture in a structural ceramic can often be traced to a preexisting flaw that was inadvertently introduced during fabrication. In a long-standing collaborative effort with the Instrumentation and Nondestructive Evaluation (INDE) Section, the Ceramics Section is characterizing the fracture behavior of structural ceramics and composites containing well-defined flaws. Samples of silicon nitride and its composites with Si_3N_4 -whisker reinforcement have been fabricated by both cold and hot pressing with appropriate additives. The fracture stress, fracture toughness, and elastic modulus of these samples are being evaluated and correlated with the fractographically located critical flaws to establish the effects of the flaws. We are evaluating these ceramics and composites in both green (cold-pressed) and fired states in an attempt to find correlations between flaw population (strength distribution) of green specimens and the corresponding densified specimens. Understanding the effects of these flaws on fracture behavior will help in development of ceramic and composites with improved mechanical properties. The results are being used by the INDE Section to guide the development of nondestructive testing methods. In a related program, we are evaluating how the mechanical properties of ceramic matrix composites are affected by the interfacial properties between ceramic whiskers (or continuous fibers) and matrix. The interface characteristics between the ceramic matrix and whisker/fiber are evaluated by mechanical testing (fiber pushout test) and electron microscopy and are correlated with the mechanical properties (strength, toughness) of composites. These correlations will provide information for designing and developing appropriate interface characteristics for thorough control of processing parameters. The results of this study will aid in the development of improved ceramic composites.

Solid Oxide Fuel Cells

Development of all-ceramic fuel cells employing yttria-stabilized zirconia as the electrolyte has been carried out in concert with ANL's Chemical Technology Division. The goal is to produce a compact and lightweight fuel cell array that can operate with a wide range of fossil fuels. In addition to the zirconia electrolyte, the fuel cell has three other ceramic components: (a) a strontium-doped lanthanum chromite interconnect, (b) a strontium-doped lanthanum manganite cathode, and (c) a cermet anode fabricated from a mixture of nickel and yttria-stabilized zirconia. These components have been formed into thin sheets and laminated into a honeycomb structure with open channels 0.040 to 0.050 in. wide. The channels allow fuel and air to flow to the active cell areas. The emphasis in the present program is on evaluating the effects of dopant on the sintering kinetics of the interconnect. Support for this program is from the DOE Office of Fossil Energy, subcontracted through Allied Signal, Inc. This funding arrangement promotes the transfer of this technology to the private sector.

Refractories Research

The Section is renewing its efforts in advanced refractory materials for iron and steelmaking. A recent small program funded by Magneco/Metrel and the State of Illinois is aimed at developing castable refractories based on sol-gel technology for a variety of uses, primarily in iron- and steelmaking with improved corrosion and thermal stress properties.

Uses would include ladles, ladle treatment vessels, and furnace linings. Refractories with various compositions are fabricated at Magneco/Metrel with different heat treatments. Subsequently, the microstructure, phase composition, and corrosion properties of these refractories are evaluated at ANL. A correlation between microstructure and properties provides information for optimizing refractory compositions with improved properties. Magneco/Metrel is a major supplier of refractory castables for the continuous casting of steel; it supplies castable refractories for other industries as well. In cooperation with Magneco/Metrel, the Section is preparing proposals for follow-on work that will rely on expertise and facilities established in the Section during a long-funded program to support refractories development for slagging coal gasifiers.

Materials Development Work for Actinide Recycle Project

The processes for the recovery of actinides from light water reactor (LWR) fuels for use in the Integral Fast Reactor (IFR) require containment vessels, stirrers, filters, and transfer tubings. For these processes, calcium is used to reduce oxide fuel and many of the fission products. This reduction is followed by operations to separate uranium from other actinides. The CaO formed during the reduction process is electrochemically reduced to calcium metal and is then recycled to minimize wastes. The liquid metal solvents, such as copper-magnesium and zinc-magnesium, cadmium, and molten calcium and alkaline earth halide salts, used in actinide processing must not react with containers and other components. In addition, for repeated use of the containers and components, these metals, salts, and radioactive materials should not wet them; the materials should also withstand high temperature, be chemically stable, possess good mechanical properties, and have good thermal shock resistance. The materials should be sufficiently dense or porous, depending on the specific applications, and still have the mechanical integrity needed in the aggressive chemical and thermal environments that will be encountered. The technology for component fabrication should allow scale-up from laboratory to commercial level.

Candidate materials for high-temperature operations can be either refractory metals or ceramics or cermets. Refractory metals are difficult to fabricate and therefore, the focus is on the development of ceramic materials. Two criteria were used to select materials for corrosion tests: one was based on thermodynamic stability and the other on thermal-shock resistance. Based on these criteria, we identified a number of oxides (i.e., magnesium oxide, yttrium oxide, calcium zirconate, calcium yttrate, calcium titanate), nitrides (i.e., aluminum nitride, titanium carbonitride, titanium nitride), carbides (i.e., titanium carbide, titanium carbonitride, and tantalum carbide), and a nitrided refractor metal alloy, Nb-30 wt.% Ti-20 wt.% W (Tribacor 532N). Thermodynamic calculations, corrosion and thermal shock experiments on these materials have shown that the oxides are not suitable. Of the several materials tested, titanium nitride, titanium carbide, titanium carbonitride, and tantalum carbide have performed well. Graphite is not compatible, but coating of graphite with some of the stable materials looks promising. Tribacor 532N has excellent thermal shock resistance, but is subject to environmentally induced cracking after exposure to liquid metal alloys containing salt. Cracking of Tribacor 532N is currently under investigation. This materials development work is being performed in cooperation with the Chemical Technology Division.

Laboratory Exchange Program

We continue to be a strong supporter of ANL's laboratory exchange program. Under this program, selected scientists from the research laboratories of major U.S. corporations spend a year at ANL. After the highly successful term of Dr. Marc Kullberg (Amoco), Mr. Mike Anderson of Magneco/Metrel and Mr. Marc Kleefisch of Amoco have joined the Ceramics Section. Mr. Kleefisch's extensive experience in catalysis, oxidatively coupled chemical reactions in an energy-related field, and chemical stability of materials will be applied in the development of dense ceramic membrane tubes for direct conversion of natural gas into high-value-added products. Mr. Kleefisch will gain experience in fabrication of various ceramic membrane tubes, which will be used in the reactor for conversion reactions at Amoco. Amoco has large reserves of methane (natural gas) of marginal economic value. The value (to Amoco and to the United States) of these reserves would be greatly enhanced if the methane could be economically converted to syngas, methanol, formaldehyde, or oxidatively coupled products such as ethylene. Mr. Anderson's extensive experience in refractory fabrication will be applied in the development of refractories (through sol-gel technology) with improved mechanical and corrosion properties. He will gain experience in microstructural evaluation and its correlation with refractory properties, which will be very valuable for refractory development at Magneco/Metrel.

Recent Work by the Ceramics Section

Publications

U. Balachandran, H. N. Frase, T. Suratwala, R. B. Poeppel, and P. Haldar (Intermagnetics General Corp.), Phase Evolution in the Pb-Doped BSCCO System, INVITED ABSTRACT for presentation at 6th Ann. Conf. on Superconductivity and Applications, Sept. 15-17, 1992, Buffalo, NY.

U. Balachandran, H. N. Frase, T. J. Brent, R. B. Poeppel, R. P. Kurosky (Seattle Specialty Ceramics), and G. S. Smith (Seattle Specialty Ceramics), Calcination and Sintering of Pb-Doped BSCCO Superconductors, submitted for presentation at 3rd Intl. Sci. and Tech. Congress, Nov. 1-4, 1992, San Francisco.

U. Balachandran, T. Suratwala, R. B. Poeppel, L. R. Motowildo (IGC Advanced Superconductors, Inc.), J. G. Hoehn (Intermagnetics General Corp.), and P. Haldar (Intermagnetics), Formation of Bi-2223 Phase and Interface Microstructure in Ag-Clad Superconductors, to be presented at Fall Mtg. of Mater. Research Soc., Nov. 30-Dec. 4, 1992, Boston.

U. Balachandran, S. L. Morissette, J. J. Picciolo, J. T. Dusek, R. B. Poeppel, S. Pei (Amoco Oil Co.), M. S. Kleefisch (Amoco), R. L. Mievile (Amoco), T. P. Kobylinski (Amoco), and C. A. Udovich (Amoco), Fabrication of Ceramic Membrane Tubes for Direct Conversion of Natural Gas, to be published in Proc. 1992 Intl. Gas Research Conf. (IGRC 92), Orlando, FL, Nov. 16-19, 1992.

U. Balachandran, C. A. Youngdahl, R. B. Poeppel, P. Haldar (Intermagnetics General Corp.), J. G. Hoehn, Jr. (Intermagnetics), J. A. Rice (Intermagnetics General Corp.), and L. R. Motowildo (IGC Advanced Superconductors, Inc.), Fabrication and Characterization of Long Lengths of Silver-Clad Bi-2223 Tapes, INVITED ABSTRACT for presentation at 1992 TMS Fall Mtg., Symp. on High Temperature Superconducting Compounds: Processing and Related Properties, Chicago, Nov. 1-5, 1992.

U. Balachandran, S. E. Dorris, M. T. Lanagan, and R. B. Poeppel, Bulk Synthesis, Reaction Kinetics, and Powder-in-Tube Processing of BSCCO Superconductors, presented at Intl. Workshop on Superconductivity, "Controlled Growth of Single- and Poly-Crystals of High Temperature Superconductors," Honolulu, June 23-26, 1992, pp. 342-343

U. Balachandran, S. L. Morissette, M. C. Hash, R. B. Poeppel, L. R. Motowildo (IGC), J. G. Hoehn (Intermagnetics General Corp.), and P. Haldar, Interface Microstructure and Formation of Bi-2223 Phase in Powder-in-Tube Processed Conductors, presented at 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

U. Balachandran, S. E. Dorris, M. T. Lanagan, and R. B. Poeppel, Bulk Synthesis, Reaction Kinetics, and Powder-in-Tube Processing of Bi-Pb-Sr-Ca-Cu-O Superconductors, presented at Intl. Workshop on Superconductivity, Honolulu, June 23-26, 1992, pp. 342-343

U. Balachandran, R. B. Poeppel, and A. K. Gangopadhyay (Northwestern U.), Recent Results in Characterization of Melt-Grown and Quench-Melt-Grown YBCO Superconductors, INVITED PAPER presented at TCSUH Workshop on HTS Mater., Bulk Processing, and Bulk Applications, Feb. 27-28, 1992, Houston.

U. Balachandran, S. E. Dorris, M. T. Lanagan, R. B. Poeppel, J. M. Tourre (Rhone-Poulenc), and J. W. Golowski (Rhone-Poulenc), Synthesis of Rare-Earth-Based Oxides for the Ceramic Industry: From Laboratory to Pilot Plant, for publication in Proc. 1991 Fall Mtg. of Mater. Res. Soc.: Symp. on Synthesis and Processing of Ceramics, Boston, Dec. 2-6, 1991.

U. Balachandran, R. B. Poeppel, A. K. Gangopadhyay (Northwestern U.), and V. Dravid (NU), Recent Results in Processing and Characterization of Melt-Grown and Quench-Melt-Grown YBCO Superconductors, presented at 1992 TCSUH Workshop on HTS Materials, Bulk Processing, and Bulk Applications, Feb. 27-28, 1992, Houston.

U. Balachandran, M. Foley, R. B. Poeppel, R. P. Kurosky, and G. S. Smith (Seattle Specialty Ceramics), Processing of $Ba_{1-x}K_xBiO_3$ Superconductors, presented at 94th Ann. Mtg. and Exposition of Am. Ceram. Soc., April 12-16, 1992, Minneapolis.

U. Balachandran, S. L. Morissette, S. E. Dorris, J. J. Picciolo, R. B. Poeppel, and H. U. Anderson (U. of Missouri-Rolla), Development of Air Sinterable Doped $LaCrO_3$ for Solid Oxide Fuel Cell Applications, presented at 94th Ann. Mtg. and Exposition of Am. Ceram. Soc., April 12-16, 1992, Minneapolis.

U. Balachandran, R. B. Poeppel, W. A. Ferrando, S. D. Karmarkar, J. Kerr, P. W. Hesse, and A. P. Divecha (Naval Surface Warfare Center), Recent Advances in Processing and Fabrication of Ceramic Superconductors, INVITED PAPER: in Phys. and Mater. Sci. of High Temperature Superconductors, II, ed. R. Kossowsky, Kluwer Academic Publishers, pp. 721-737 (1992).

U. Balachandran, R. B. Poeppel, J. M. Tourre (Rhone-Poulenc), and J. W. Golowski (Rhone-Poulenc), The Synthesis of Rare-Earth Based Oxides for the Ceramic Industry: From Laboratory to Pilot Plant, presented at 1991 Fall Mtg. of Materials Research Soc., Boston, Dec. 2-6, 1991.

U. Balachandran, T. Suratwala, C. A. Youngdahl, J. R. Hull, R. B. Poeppel, V. Dravid (Northwestern U.), and L. D. Marks (NU), Processing, Microstructure, and Properties of Quench-Melt-Grown YBCO Superconductors, presented at 1992 TMS Annual Mtg., Symp. on High Tc Superconductivity in Bulk, San Diego, March 1-5, 1992.

U. Balachandran, S. E. Dorris, M. T. Lanagan, K. C. Goretta, and R. B. Poeppel, Reduced-Pressure Calcination of Bismuth-Based Superconductors, presented at 1991 Fall Mtg. of Mat. Research Soc., Boston, Dec. 2-6, 1991.

U. Balachandran, J. J. Picciolo, J. T. Dusek, R. A. Russell, R. B. Poeppel, and R. L. Mievile (Amoco Oil Co.), Fabrication of Ceramic Membrane Tubes for Direct Electrochemical Conversion of Natural Gas, to be presented at 1992 Intl. Gas Research Conf. (IGRC 92), Orlando, FL, Nov. 16-19, 1992.

U. Balachandran, S. E. Dorris, M. T. Lanagan, K. C. Goretta, J. P. Singh, C. A. Youngdahl, J. J. Picciolo, J. T. Dusek, and R. B. Poeppel, Recent Improvements in Processing and Fabrication of High-Temperature Superconductors, INVITED PAPER presented at Intl. Conf. on Transparent Ferroelectric Ceramics: Production, Properties, and Applications, Oct. 1-4, 1991, Riga, Latvia.

U. Balachandran, T. J. Brent, and R. B. Poeppel, Preparation of $\text{YBa}_2\text{Cu}_3\text{O}_x$ Using BaCuO_2 , Y_2O_3 , and CuO , presented at 44th Pacific Coast Regional Mtg. of Am. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

U. Balachandran, R. B. Poeppel, W. A. Ferrando, S. D. Karmarkar, J. Kerr, and A. P. Divecha (Naval Surface Warfare Ctr.), Recent Advances in Processing and Fabrication of Ceramic Superconductors, INVITED PAPER presented at NATO Advanced Study Institute: Physics and Material Science of High- T_c Superconductors-II, Aug. 18-31, 1991, Porto Carras, Greece.

U. Balachandran and R. B. Poeppel, Defect Structure of Donor-Doped Perovskites, INVITED ABSTRACT presented to Intl. Conf. on Transparent Ferroelectric Ceram: Products, Properties, and Applications, Oct. 1-4, 1991, Riga, Latvia.

U. Balachandran, R. A. Russell, S. L. Morissette, T. J. Brent, and R. B. Poeppel, Preparation of $\text{YBa}_2\text{Cu}_3\text{O}_x$ Superconductor Via Ternary Precursors, Proc. 2nd Intl. Ceramic Society's Electronics Division Mtg., Orlando, FL, Nov. 12-15, 1990, Superconductivity II, Reprinted from Ceram. Trans., Vol. 18, 1991, pp. 181-190.

U. Balachandran, S. L. Morissette, R. A. Russell, S. E. Dorris, and R. B. Poeppel, Formation of Intermediate Compounds During Reduced-Pressure Calcination of Y-Ba-Cu-O Precursor, Proc. 3rd Intl. Symp. on High-Temperature Superconductors: Processing and Microstructure Property Relationships, 1991 TMS Ann. Mtg. and Exhibition, New Orleans, eds. S. H. Whang, A. DasGupta, and E. Collings, Feb. 17-21, 1991, pp. 273-280.

U. Balachandran, Y. Li (MSD), Y. Gao (MSD), K. L. Merkle (MSD), H. Shi (MSD), and R. B. Poeppel, Preparation and Characterization of $\text{YBa}_2\text{Cu}_4\text{O}_8$ Superconductor, Proc. 2nd Intl. Ceramic Science and Tech. Congress and Am. Ceram. Soc.'s Electronics Div. Mtg., Orlando, FL, Nov. 12-15, 1990, Superconductivity II, reprinted from Ceram. Trans., Vol. 18, 1991, pp. 271-282.

U. Balachandran, R. B. Poeppel, S. E. Dorris, C. Z. Zhang, D. Xu, K. Merkle (MSD), Y. Gao (MSD), Y. Li (MSD), J. J. Picciolo, J. T. Dusek, and G. Selvaduray (San Jose State U.), Characterization of YBCO Superconductor Sintered in CO_2 -Containing Atmosphere, INVITED PAPER: Proc. 2nd Intl. Ceram. Sci. and Tech. Congress and Am. Ceram. Soc. Electronics Division Mtg, Orlando, FL, Nov. 12-15, 1990, Superconductivity II, reprinted from Ceram. Trans. Vol 18, 1991, pp. 341-355.

U. Balachandran, D. Xu, C. Zhang, S. E. Dorris, R. A. Russell, T. Gao (MSD), K. L. Merkle (MSD), J. T. Dusek, J. J. Piccolo, and R. B. Poeppel, and G. Selvaduray (San Jose State U.), Effects of Atmosphere and Heating Rate During Processing of a Ceramic Superconductor, INVITED PAPER: Proc. 3rd Intl. Symp. on *High-Temp. Superconductors: Processing & Microstructure Property Relationships*, 1991 TMS Annual Mtg. & Exhibition, New Orleans, Feb. 17-21, 1991, eds. S. H. Whang, A. DasGupta, and E. Collings, The Minerals, Metals & Materials Soc., 1991, pp. 257-271.

U. Balachandran, R. B. Poeppel, and J. G. Hunt (Atek Metals Center, Inc.), Hot Extrusion of High-Temperature Superconducting Oxides, *Ceramic Bulletin*, Vol. 70, No. 5, May 1991, pp. 813-816.

A. C. Blondo, M. T. Lanagan, S. E. Dorris, K. C. Goretta, R. B. Poeppel, and J. S. Kallend (IIT), Texture Studies of Pb-doped Bi-Sr-Ca-Cu-O Thick Films, presented at Spring Mtg. of Mater. Res. Soc., April 27-May 1, 1992, San Francisco.

A. C. Blondo, K. C. Goretta, D. Shi (MSD), R. B. Poeppel, and J. S. Kallend (IIT), Effects of Processing Parameters and Texture on Properties of Melt-textured $\text{YBa}_2\text{Cu}_3\text{O}_x$, presented at 44th Pacific Coast Regional Mtg. of Amer. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

A. C. Blondo, C. T. Wu (Illinois Inst. of Tech.), S. Wu, J. Schwartz (U. of Illinois at Urbana-Champaign), K. C. Goretta, and R. B. Poeppel, Texture and Properties of Ag-Sheathed Bi-Sr-Ca-Cu-O Wires, Poster and abstract for presentation at Review Mtg. for Sci. and Tech. Ctr. for Superconductivity, Sept. 12-13, 1991, Urbana, IL.

A. C. Blondo, J. S. Kallend (IIT), A. J. Schultz (CHM), and K. C. Goretta, Texture Evolution During Sintering of Y-Ba-Cu-O, Proc. 3rd Intl. Symp. on *High-Temp. Superconductors: Processing & Microstructure Property Relationships*, New Orleans, Feb. 17-21, 1991, pp. 119-127.

R. Birkhahn, N. Browning, C. A. Youngdahl, M. T. Lanagan, and R. B. Poeppel, Interfacial Resistance Between Ceramic Superconductor and Silver, submitted to *Applied Superconductivity*, July 1992.

I. D. Bloom, J. M. Frommelt, M. C. Hash (ETP), M. T. Lanagan, C. T. Wu, and K. C. Goretta, Synthesis of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, submitted to *Mater. Res. Bull.*

M. A. Boling, M. T. Lanagan, S. E. Dorris, D. Y. Kaufman, C. A. Youngdahl, C. T. Wu, and R. B. Poeppel, Effect of Thermal Processing Conditions on Ag-Sheathed $(\text{Bi,Pb})_2\text{Sr}_2\text{Cu}_3\text{O}_y$ Tapes, presented at 94th Ann. Mtg. and Expo. of Amer. Ceram. Soc., April 12-16, 1992, Minneapolis.

M. Cankurtaran, G. A. Saunders, K. C. Goretta, and R. B. Poeppel, Ultrasonic Determination of the Elastic Properties and Their Pressure/Dependences and Temperature in Very Dense $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, *Physical Review B*, Vol. 46, No. 2, July 1992, pp. 1157-1165.

M. Cankurtaran and C. A. Saunders (U. of Bath, UK), K. C. Goretta, and R. B. Poeppel, Elastic Properties under Pressure of Very Dense $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, Presented at Condensed Matter and Mater. Phys. Conf. (CMMP-91), Birmingham City Centre, UK, Dec. 17-19, 1991.

M. Cankurtaran (U. of Bath, UK), G. A. Saunders (U. of Bath, UK), K. C. Goretta, and R. B. Poeppel, Ultrasonic Determination of the Elastic Moduli and their Pressure Dependences in Very Dense $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, submitted to Superconductor Science and Technology.

C. L. Carvalho, D. I. dos Santos, R. R. de Silva, M. A. Aegerter, and U. Balachandran, Superconducting Films Made By Solution Techniques, presented at 93rd Ann. Mtg. and Exposition of the Am. Ceram. Soc., Cincinnati, April 28-May 2, 1991.

Y. S. Cha, S. E. Dorris, J. R. Hull, and R. B. Poeppel, The Effect of Processing Parameters during Heat Treatment of Bulk High- T_c Superconductors, INVITED PAPER: Proceedings 1991 ASME Winter Annual Mtg., Session on Bulk Processing and Mechanical Properties of High- T_c Superconductors, Atlanta, Dec. 1-6, 1991, The American Society of Mechanical Engineers, New York, 1992, 91-WA-AES-3, pp. 1-9.

N. Chen, J. L. Routbort, K. C. Goretta, J. P. Singh, and R. B. Poeppel, Grain Size Control in Bulk $\text{YBa}_2\text{Cu}_3\text{O}_x$, presented at Intl. Workshop on Superconductivity, "Controlled Growth of Single- and Poly-Crystals of High Temperature Superconductors," Honolulu, June 23-26, 1992.

N. Chen, S. J. Rothman, J. L. Routbort, and K. C. Goretta, Tracer Diffusion of Ba and Y in $\text{YBa}_2\text{Cu}_3\text{O}_x$, Submitted to J. Mater. Res.

Nan Chen (MSD), K. C. Goretta, W. Wu, R. A. Olson, R. B. Poeppel, and A. S. Nash (Marquette U.), Sintering of Bulk High- T_c Superconductors: $\text{YBa}_2\text{Cu}_3\text{O}_x$, submitted to 1992 Powder Metallurgy World Congress, June 21-26, 1992, San Francisco.

Nan Chen (MSD), C. T. Wu, M. T. Lanagan, K. C. Goretta, and R. B. Poeppel, Processing $\text{TlBa}_2\text{Ca}_2\text{Cu}_3\text{O}_x/\text{Ag}$ wires, presented at Ann. Mtg. of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

C. Y. Chu, J. L. Routbort, N. Chen, A. C. Blondo, D. S. Kupperman, and K. C. Goretta, Mechanical Properties and Texture of Dense Polycrystalline $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, Superconductor Sci. and Tech. 5, 306-312 (1992).

C. Y. Chu, J. L. Routbort, K. C. Goretta, J. Joo, and J. P. Singh, Comparison of Microstructures and Mechanical Properties of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ Superconductors Densified by Various Methods, submitted to 1991 Fall Mtg. of Materials Res. Soc., Boston, Dec. 2-6, 1991.

C. Y. Chu and J. P. Singh, Microscopic Characterization of B- Si_3N_4 Whiskers in Hot-Pressed Si_3N_4 Composites, presented at 94th Ann. Mtg. of Amer. Ceram. Soc., April 12-16, 1992, Minneapolis.

C. Y. Chu (MSD), J. P. Singh, and J. L. Routbort (MSD), High-Temperature Failure of Hot-Pressed Si_3N_4 and Its Si_3N_4 Whisker Composites, submitted to J. Amer. Ceram. Soc.

S. Danyluk, M. J. McNallan (Superconducting Products Co.), R. Troendly (SP Co.), M. T. Lanagan, K. C. Goretta, and R. B. Poeppel, Fabrication of Bi-Sr-Ca-Cu-O/Ag Coils, presented at Intl. Workshop on Superconductivity, Controlled Growth of Single- and Poly-Crystals of High Temperature Superconductors, Honolulu, June 23-26, 1992.

S. Danyluk (U. of Illinois at Chicago), Y. Fang (UIC), K. C. Goretta, and R. B. Poeppel, Measurement of Friction and Wear in Bulk $\text{YBa}_2\text{Cu}_3\text{O}_x$ and $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$ Superconductors, INVITED ABSTRACT submitted to Fall Mtg. of the Metallurgical Soc., Chicago, Nov. 1-5, 1992.

S. Danyluk, A. P. Acosta, A. Figueroa, J. Gazda, D. Y. Kaufman, M. Solari (U. of Illinois at Chicago), M. T. Lanagan, C. T. Wu, and K. C. Goretta, Solid State Synthesis of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, To be presented at 1991 Fall Mtg. of Mater. Res. Soc., Boston, Dec. 2-6, 1991.

A.R. De Arellano-Lopez (U. of Seville, Spain), A. Dominguez-Rodriguez (U. of Seville), K. C. Goretta, and J. L. Routbort, Plastic Deformation Mechanisms in SiC-Whisker-Reinforced Al_2O_3 , Submitted to J. Amer. Ceram. Soc., May 1992.

L. P. de Rochemont, C. E. Oakes, M. R. Squillante (Radiation Monitoring Devices); A. M. Herman (U. of Colorado); R. J. Andrews (Hanson Air Force Base, MA); R. B. Poeppel; R. J. Weggel and J. E. C. Williams (Mass. Inst. of Tech.); I. A. Carberg and W. C. Kelliher (NASA Langley Res. Ctr), Recent Progress Towards Developing a Superconducting Magnet for Magnetic Suspension Balance Systems using High- T_c Ceramic Superconductors, Submitted to the Intl. Symp. on Magnetic Suspension Tech., NASA Langley Research Center, Hampton, VA, Aug. 19-23, 1991.

M. R. DeGuire (Case Western Reserve U.), U. Balachandran, S. E. Dorris, S. Morissette, and R. B. Poeppel, Coprecipitation Synthesis of Doped Lanthanum Chromite, presented at 94th Ann. Mtg. of Am. Ceram. Soc., Minneapolis, April 12-16, 1992.

A. Dominguez-Rodriguez (U. of Seville, Spain), J. Castaing (LPM, CNRS, France), K. C. Goretta, and J. L. Routbort, Creep and Diffusion in Nonstoichiometric Oxides, Symp. on Point Defects Related Properties of Ceramics, 93rd Annual Mtg. of Amer. Ceram. Soc., Cincinnati, April 28-May 2, 1991, Ceramic Transactions, Vol. 24, pp. 130-150.

S. E. Dorris, I. Bloom, M. C. Hash, and M. Krumpelt, Sealant Research for SOFC, presented at 4th Ann. Fuel Cells Contractors' Review Mtg., Morgantown, WV, July 14-15, 1992.

S. E. Dorris, I. Bloom, M. C. Hash, and M. Krumpelt, Sealant Research for SOFC, presented at 4th Ann. Fuel Cells Contractor's Review Mtg., Morgantown, WV, July 14-15, 1992.

S. E. Dorris, J. J. Picciolo, J. T. Dusek, C. A. Youngdahl, M. T. Lanagan, and R. B. Poeppel, High-Current Superconducting Conductor: Progress Report for the Period Ending Dec. 10, 1991, Progress Report submitted to Tokyo Electric Power Co. in compliance with WFO proposal agreement.

S. E. Dorris, J. T. Dusek, M. T. Lanagan, J. J. Picciolo, J. P. Singh, J. E. Creech, and R. B. Poeppel, Extrusion of Multilayer Superconductor Coils, INVITED PAPER: Amer. Ceram. Soc. Bulletin, Vol. 70, No. 4, 1991, pp. 722-726

D. I. dos Santos, C. L. Carvalho, R. R. da Silva, and M. A. Aegerter (Brazil), U. Balachandran and R. B. Poeppel, Superconducting Films Made by Spin-Coating of Acetate Solutions, Ceramic Transactions - Superconductivity and Ceram. Superconductors II, eds., K. Nair, U. Balachandran, Y.-M. Chiang, and A. S. Bhalla; The Am. Ceram. Soc., Inc., Westerville, OH, pp. 441-452 (1991).

V. P. Dravid, H. Zhang (Northwestern U.), and U. Balachandran, High Resolution TEM and Analytical Electron Microscopy of Quench-Melt-Grown High- T_c Superconductors, presented at 1991 Fall Mtg. of Mater. Res. Soc., Boston, Dec. 2-6, 1991.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. L. Dieckman, D. Singh, E. A. Sivers, and S. H. Sheen, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, to be published in Proc. 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, on May 14-16, 1992.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. L. Dieckman, D. Singh, E. A. Sivers, and S. H. Sheen, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, to be published in Proc. 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1992.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. H. Sheen, D. Singh, E. A. Sivers, and S. L. Dieckman, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, presented at 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1992.

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, A. S. Wagh, C.-Y. Chu, and T. Leuthi, Development of Nondestructive Evaluation Methods of Effects of Flaws on the Fracture Behavior of Structural Ceramics, Proc. 5th Annual Conf. on Fossil Energy Materials - May Conf., Oak Ridge, TN, May 13-16, 1991, CONF-9105184, ORNL/FMP-91/1, pp. 137-153.

A. K. Gangopadhyay (Northwestern U.) and U. Balachandran, Flux Pinning and Irreversibility Temperature in Melt-Grown, Quench-Melt-Grown, and Sintered $YBa_2Cu_3O_{6+y}$, presented at 94th Ann. Mtg. and Expo. of the Am. Ceram. Soc., April 12-16, 1992, Minneapolis.

K. B. Garg, N. L. Saini, P. Srivastava (Rajasthan U., India) and U. Balachandran, Synthesis and Characterization of $YBa_2Cu_{3-x}Ni_xO_7$ Compounds, presented at 2nd Intl. Ceramic Sci & Tech. Congress and Am. Ceram. Soc. Electronics Div. Mtg., Orlando, FL., Nov. 12-15, 1990.

K. C. Goretta, M. T. Lanagan, D. Y. Kaufman, A. C. Biondo, C. T. Wu, M. E. Loomans, M. R. Cheesman, R. B. Poeppel, and A. S. Nash, Sintering of Bulk High- T_c Superconductors: Bi-Sr-Ca-Cu-O, to be published in Proc. 1992 Powder Metallurgy World Congress, June 21-26, 1992, San Francisco.

K. C. Goretta, N. Chen, M. T. Lanagan, W. Wu, J. P. Singh, R. A. Olson, J. L. Routbort, and R. B. Poeppel, Sintering of Bulk High- T_c Superconductors: Y-Ba-Cu-O, to be published in Proc. 1992 Powder Metallurgy World Congress, June 21-26, 1992, San Francisco.

K. C. Goretta, C.-T. Wu, M. T. Lanagan, M. A. Boling, D. Shi, D. J. Miller, N. Chen, W. G. Hanewald, S. Sengupta, Z. Wang, R. B. Poeppel, F. Foong, and S. H. Liou (U. of Nebraska), Processing and Properties of Silver-Clad Tl-Ba-Ca-Cu-O Wires and Tapes, submitted for publication in Proc. 1992 Spring Mtg. of Materials Res. Soc., San Francisco, April 27-May 1, 1992.

K. C. Goretta, N. Chen, M. T. Lanagan, S. E. Dorris, J. Hu, C. T. Wu, and R. B. Poeppel, Processing TlBa₂Ca₃O_x Powders, Submitted to Superconductor Science and Technology.

K. C. Goretta, D. J. Miller, R. B. Poeppel, A. S. Nash (Marquette U.), Characterization of Hot Isostatically Pressed Bi-Sr-Ca-Cu-O as a Function of Consolidation Variables, Mat. Res. Soc. Symp. Proc. Vol. 251 (1991 Materials Research Society Fall Mtg., Symp. S: Gas Pressure Effects on Materials., Boston, Dec. 2-6, 1991, pp. 325-330.

K. C. Goretta, M. L. Kullberg, D. Bar, G. A. Risch, and J. L. Routbort, Fracture Toughness of YBa₂Cu₃O_x Containing Y₂BaCuO₅ and ZrO₂, Superconductor Science and Technology, 4 (1991) pp. 544-547, printed in UK.

K. C. Goretta, C. T. Wu, A. C. Biondo, M. R. Cheesman, R. B. Poeppel, and A. S. Nash (Marquette U.), Sintering of Bulk High- T_c Superconductors: Bi-Sr-Ca-Cu-O, submitted to 1992 Powder Metallurgy World Congress, June 21-26, 1992, San Francisco.

K. C. Goretta; J. L. Routbort, D. J. Miller (MSD); A. Dominguez-Rodriguez, C. Clauss (U. of Seville, Spain), and A. S. Nash (Marquette U.), Compressive Creep of Bi₂Sr₂CaCu₂O_x, presented at Ann. Mtg. of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

K. C. Goretta, C. T. Wu, M. T. Lanagan, M. A. Boling, W. G. Hanewald, R. B. Poeppel, D. Shi, D. J. Miller, Nan Chen (MSD), F. Foong, and S. H. Liou (U. of Nebraska), Processing and Properties of Silver-Clad Tl-Ba-Ca-Cu-O Wires and Tapes, submitted to 1992 Spring Mtg. of Mater. Res. Soc., San Francisco, April 27-May 1, 1992.

K. C. Goretta, R. B. Poeppel, and A. S. Nash (Marquette U.), Characterization of Hot Isostatically Pressed Bi-Sr-Ca-Cu-O as a Function of Consolidation Variables, submitted to 1991 Mater. Res. Soc. Fall Mtg., Boston, Dec. 2-6, 1991; Symp. Q: Synthesis and Processing of Ceramics.

K. C. Goretta, W. Wu, C. T. Wu, D. Xu, C. A. Youngdahl, D. Shi (MSD), J. P. Singh, J. J. Picciolo, M. T. Lanagan, J. R. Hull, J. T. Dusek, S. E. Dorris, N. Chen (MSD), A. C. Biondo, U. Balachandran, and R. B. Poeppel, High- T_c Superconductors: Fabricating Technologies and Future Perspectives, Mater. Chem. and Phys., 31, (1992) pp. 73-78.

K. C. Goretta, M. T. Lanagan, M. A. Boling, D. Shi (MSD), N. Chen (MSD), R. B. Poeppel, and C. T. Wu (IIT), Processing and Properties of Tl-Ba-Ca-Cu-O/Ag Wires, presented to Fall Mtg. of the Mater. Research Soc., Boston, Dec. 2-6, 1991.

K. C. Goretta, High- T_c Superconductors: Fabricating Technologies and Future Perspectives, INVITED PAPER presented at 2nd Workshop on Basic and Applied Aspects of Rare Earths, Venice, Italy, May 9-10, 1991.

P. Haldar (Intermagetics General Corp.), J. G. Hoehn, Jr. (Intermagetics), J. A. Rice (Intermagetics), L. R. Motowidlo (IGC Advanced Superconductors, Inc.), U. Balachandran, C. A. Youngdahl, and R. B. Poeppel, Characteristics of Small Superconducting Coils Fabricated from Long Lengths of Silver Clad Bi-2223 Tapes, presented at Intl. Workshop on Superconductivity, Honolulu, June 23-26, 1992, pp. 374-375.

P. Haldar (Intermagetics General Corp.), J. G. Hoehn (Intermagetics), M. S. Walker (Intermagetics), L. R. Motowidlo (IGC Advanced Superconductors, Inc.), U. Balachandran, and C. A. Youngdahl, Fabrication and Properties of High- T_c Tapes and Coils Made from Silver-Clad Bi-2223 Superconductors, presented at 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

P. Haldar (Intermagetics General Corp.), J. G. Hoehn (Intermagetics), J. A. Rice (Intermagetics General Corp.), L. R. Motowidlo (IGC Advanced Superconductors, Inc.), U. Balachandran, C. A. Youngdahl, and R. B. Poeppel, Characteristics of Small Superconducting Coils Fabricated from Long Lengths of Silver Clad Bi-2223 Tapes, presented at Intl. Workshop on Superconductivity, June 23-26, 1992, Honolulu, pp. 374-375.

J. R. Hull and R. B. Poeppel, Development of High-Temperature Superconductor Applications at Argonne National Laboratory, presented at 1992 TCSUH Workshop on HTS Materials, Bulk Processing, and Bulk Applications, Houston, Feb. 27-28, 1992.

F. G. Jones (Pennsylvania State U.), T. R. Shrout (Pennsylvania State U.), S. J. Jang (PSU), and M. T. Lanagan, Microwave Properties of Ferroelectric Ceramic/Polymer 0-3 Composites, Proc. 1990 IEEE 7th Intl. Symp. on Applications of Ferroelectrics, June 6-8, 1990, Champaign, IL, pp. 455-458.

J. Joo, J. P. Singh, R. B. Poeppel, A. K. Gangopadhyay (Northwestern U.), and T. O. Mason (NU), Effect of Ag Solubility on Microstructure and Superconducting Properties of $YBa_2Cu_3-xAg_xO_{7-\sigma}$ Superconductors, J. Applied Physics 71 (5), March 1992.

J. Joo, J. P. Singh, R. B. Poeppel, A. K. Gangopadhyay (Northwestern U.), and T. O. Mason (NU), Effects of Ag Solubility on Microstructure and Superconducting Properties of $YBa_2Cu_3-xAg_xO_{7-\sigma}$, submitted for NSF Site Visit Poster Booklet, Oct. 8-9, 1991, Urbana, IL.

J. Joo, J. P. Singh, and R. B. Poeppel, Effect of Silver Addition on Microstructure and Mechanical Properties of BSCCO Superconductors, presented at 1991 Fall Mtg. of Mater. Research Soc., Boston, Dec. 2-6, 1991.

K. R. Karasek, S. T. Gonczy (Allied-Signal Inc.), J. B. Kupperman, E. J. Zamirowski, K. C. Goretta, and J. L. Routbort, A First Look at Erosion of Continuous-Fiber-Reinforced Ceramic-Matrix Composites, submitted to Eng. Ceram. Div. 16th Annual Conf. on Composites and Advanced Ceramics, Cocoa Beach, FL, Jan. 7-10, 1992.

D. Y. Kaufman, M. T. Lanagan, S. E. Dorris, J. T. Dawley, I. D. Bloom, M. C. Hash, N. Chen, M. R. DeGuire, and R. B. Poeppel, Thermomechanical Processing of Reactivity Sintered Ag-Clad (Bi, Pb)₂Ca₂Cu₃O_x Tapes, submitted to Applied Superconductivity.

K. S. Kirkpatrick, T. O. Mason (Northwestern U.), U. Balachandran, and R. B. Poeppel, Impedance Spectroscopy Study of Sintering in Bi-doped AnO, submitted to J. Am. Ceram. Soc.

K. S. Kirkpatrick, U. Balachandran, R. B. Poeppel, and T. O. Mason (NU), Impedance Spectra Analysis During Cooling of ZnO Varistor, presented at 1992 Mater. Res. Soc. Spring Mtg., San Francisco, April 27-May 1, 1992.

D. S. Kupperman, S. Majumdar, J. S. Gregar (CD), J. P. Singh, S. Dorris, N. Gopalsami, S. Dieckman, A. C. Raptis, R. A. Valentin, and T. K. Hunt (ERIM), Materials Research for Sodium Engine Development, to be published in Proc. 26th Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

D. S. Kupperman, S. Dorris, S. H. Sheen, R. Palm (RAS), J. Dusek, and A. C. Raptis, Assessment of Tamperproof Ceramic Seals, ANL/ACTV-90/5 (1990).

D. S. Kupperman, S. Majumdar, J. P. Singh, and A. Saigal, The Application of Neutron Diffraction Time-of-Flight Measurements to the Study of Strain in Composites, INVITED PAPER presented at NATO Advanced Research Workshop on "Measurement of Residual Stress & Applied Stress Using Neutron Diffraction," Oxford, UK, March 18-22, 1991.

D. S. Kupperman, S. Majumdar, and J. P. Singh, Application of Neutron Diffraction to the Determination of Residual Strain in Advanced Composites, INVITED PAPER submitted to J. Neutron News.

D. S. Kupperman, J. P. Singh, and S. Majumdar, Use of Neutron Diffraction in the Measurement of Residual Strains in Composites, presented at Ann. Spring Mtg. of Am. Ceram. Soc., Cincinnati, April 1991.

D. S. Kupperman, J. P. Singh, and R. L. Hitterman, Use of Neutron Diffraction to Determine Grain-Size Effects on Strain in YBa₂Cu₃O_{7-x}, submitted to J. Appl. Phys.

- M. T. Lanagan, S. E. Dorris, D. Y. Kaufman, N. Chen, J. Dawley, I. D. Bloom, and R. B. Poeppel, Microstructures and Electrical Properties of $\text{Pb}_{0.4}\text{Bi}_{1.8}\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}/\text{Ag}$ Composite Tapes, to be presented at Fall Mtg. of Materials Research Soc., Nov. 30-Dec. 4, 1992, Boston.
- M. T. Lanagan, S. E. Dorris, I. D. Bloom (CTD), M. C. Hash (CTD), and R. B. Poeppel, Effect of Melting Behavior on BSCCO (2223) Powder-in-Tape Tapes, presented at 9th Annual Mtg. of Amer. Ceram. Soc., April 12-16, 1992, Minneapolis.
- Y. Li, Y. Gao, K. L. Merkle, H. Shi, and U. Balachandran, Defects in Decomposed $\text{YBa}_2\text{Cu}_3\text{O}_x$ (124) Superconductor After Rapid Annealing, Mat. Res. Soc. Symp. Proc. Vol. 209 (1991) pp. 813-818.
- S. H. Liou, V. K. Chan, F. Foong, C. Y. Wu (Wichita St. U.), D. A. Meyer (Behlen Lab. of Phys. and Cntr. for Mater. Res. and Analysis), K. C. Goretta, and D. Shi, Characterization and Processing of Tl-based Superconducting Tapes, submitted to 1991 Mater. Research Soc. Fall Mtg., Boston, Dec. 2-6, 1991; Symp. H: High Temperature Superconductors.
- P. S. Maiya, S. F. Zentack, J. T. Dusek, and R. B. Poeppel, A Candidate Container Material for Pyrochemical Processes, To be presented at Symp. V: Scientific Basis for Nuclear Waste Management XVI, Mater. Res. Soc., Fall '92, Nov. 30-Dec. 4, 1992, Boston.
- P. S. Maiya, S. F. Zentack, D. Singh, D. S. Poa (CMT), D. E. Busch, and R. B. Poeppel, Evaluation of Tribacor 532N as a Container Material for Pyrochemical Applications, to be presented at 1992 TMS Fall Mtg., Nov. 1-5, 1992, Chicago.
- P. S. Maiya and T. F. Kassner, Role of Atmospheric Corrosion of Aluminum Alloys in Viability of Intrinsic-Surface Methods for Tagging Military Hardware, ANL/ACTV-91/6 (1991).
- P. S. Maiya, W. K. Soppet, J. Y. Park, T. F. Kassner, W. J. Shack, and D. R. Diercks, Stress Corrosion Cracking of Waste Container Materials, ANL-90/50 (1990).
- S. Majumdar, J. P. Singh, D. S. Kupperman, and A. D. Krawitz (U. of Missouri, Columbia), Application of Neutron Diffraction to Measure Residual Strains in Various Engineering Composite Materials, J. Eng. Mater. and Tech., Jan. 1991, Vol. 113, pp. 51-59.
- T. O. Mason, B. S. Hong, E. A. Cooper, T. A. Derouin, C. N. Pleczulewski (Northwestern U.), K. S. Kirkpatrick, U. Balachandran, R. B. Poeppel, and R. W. Siegel (MSD), Impedance Spectroscopy of Electroceramics: Processing and Properties, presented at 94th Ann. Mtg. of Am. Ceram. Soc., Minneapolis, April 12-16, 1992.
- P. McGinn (U. of Notre Dame), W. Chen (UND), N. Zhu (UND), M. T. Lanagan, and U. Balachandran, Microstructure and Critical Current Density of Zone and Melt Textured $\text{YBa}_2\text{Cu}_3\text{O}_{6+x}$, Appl. Phys. Lett. 57(14), Oct. 1990, pp. 1455-1457.
- P. J. McGinn, W. Chen, and N. Zhu (U. of Notre Dame), U. Balachandran, and M. T. Lanagan, Texture Processing of Extruded $\text{YBa}_2\text{Cu}_3\text{O}$ Wires by Zone Melting, published in Physica C, 165, North Holland, pp. 480-484, (1990).

B. M. Moon, G. Kordas, and D. J. Van Harlingen (U. of Illinois at Chicago), Y. L. Jeng and D. L. Johnson (NU), P. R. Sharpe and K. C. Goretta, Sinter Forge Process for Pb, Sb Doped 110 K BiSrCaCuO Superconducting Phase, to be published in Materials Letters.

S. L. Morissette, U. Balachandran, J. J. Picciolo, R. L. McDaniel, R. B. Poeppel, and R. L. Mieville (Amoco Oil Co.), Synthesis and Fabrication of Ceramic Membrane Tubes for Conversion of Natural Gas, presented at Spring Mtg. of Mater. Res. Soc., April 27-May 1, 1992, San Francisco, CA.

L. R. Morss (CHM), U. Balachandran, and T. B. Lindemer (ORNL), Thermochemistry of $\text{YBa}_2\text{Cu}_4\text{O}_8$ and Other Superconductor-Related Oxides, presented at 46th Calorimetry Conf., DeKalb, IL, July 28-Aug. 1, 1991.

A. S. Nash (Marquette U.), K. C. Goretta, D. J. Miller (MSD), and R. B. Poeppel, Properties of Hot Isostatically Pressed $\text{Bi}_2\text{Sr}_{1.7}\text{CaCu}_2\text{O}_x$, presented at Spring Mtg. of Mater. Res. Soc., San Francisco, April 27-May 1, 1992.

A. S. Nash (Marquette U.), K. C. Goretta, R. Wheeler IV, B. M. Moon (U. of Illinois at Urbana-Champaign), C. T. Wu (Illinois Inst. of Tech.), and P. Nash (IIT), Consolidation and Plasticity of Bi-Sr-Ca-Cu-O Superconductors, Proc. Powder Metallurgy Conf. and Exhibition, Chicago, June 9-12, 1991, Advances in Powder Metallurgy-1991, Vol. 6, pp. 371-380.

A. S. Nash (Marquette U.), P. Nash (Illinois Inst. of Tech.), R. B. Poeppel, and K. C. Goretta, Sintering and Hot Isostatic Pressing of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, Proc. Symp. on High Temperature Superconducting Compounds III, Ann. Mtg. of Metal. Soc., New Orleans, eds. S. H. Whang, A. DasGupta, and E. Collings, Feb. 17-21, 1991, pp. 315-323.

Alexis S. Nash (Marquette U.), P. Nash (IIT), H. Shi, R. B. Poeppel, and K. C. Goretta, Hot Isostatically Pressed Bi-Sr-Ca-Cu-O, Supercond. Sci. and Technol.

J. Nell and B. J. Wood (NU), S. E. Dorris, and T. O. Mason (NU), Jonker-type Analysis of Small Polaron Conductors, J. Solid State Chem. 82, 1989, pp. 247-254.

S. K. Patapis (U. of Athens), L. Sideridis (U. of Athens), G. Apostolopoulos (U. of Athens), M. Ausloos (Institute of Physique B5, Belgium), H. L. Luo U. (U. of California-LaJolla), C. Politis (Karlsruhe, Germany), T. Puig (U. of Barcelona), M. Pont (U. of Barcelona), J. S. Munoz (U. of Barcelona), and U. Balachandran, Paraconductivity Measurements and Comparative Studies of Fluctuations in BiSrCaCuO, YBaCuO, and YBaCuO with Gd Substitution, to be included in Proc. NATO Advanced Study Institute: Physics and Mater. Sci. of High- T_c Superconductors II, Aug. 18-31, 1991, Porto Carras, Greece.

R. B. Poeppel, Progress Toward Application of Bulk High T_c Superconductors, INVITED ABSTRACT presented at 3rd World Congress on Superconductivity, Munich, Germany, Sept. 14-18, 1992.

R. B. Poeppel, K. C. Goretta, U. Balachandran, S. E. Dorris, M. T. Lanagan, J. J. Picciolo, J. P. Singh, C. A. Youngdahl, and D. I. dos Santos (Unl. Estadual Paulista), Processing and Properties of Bulk High-Temperature Superconductors, INVITED PAPER submitted to Brazilian Review of Physics.

R. B. Poeppel, K. C. Goretta, U. Balachandran, I. Bloom, Y. S. Cha, S. E. Dorris, J. T. Dusek, J. E. Emerson, K. E. Gray, M. C. Hash, J. R. Hull, J. S. Kallend, R. T. Kampwirth, M. A. Kirk, D. S. Kupperman, M. T. Lanagan, V. A. Maroni, R. L. McDaniel, D. J. Miller, J. J. Picciolo, J. L. Routbort, J. P. Singh, and C. A. Youngdahl, Practical Superconductor Development for Electrical Power Applications - Annual Report for FY 1991, ANL-91/28 (1991).

R. B. Poeppel, U. Balachandran, S. E. Dorris, J. T. Dusek, K. C. Goretta, M. T. Lanagan, J. J. Picciolo, J. P. Singh, and C. A. Youngdahl, Progress Toward Commercial High- T_c Superconductors, INVITED PAPER presented at Am. Ceram. Soc. Electr. Div. and Glass and Optical Mater. Div. Joint Mtg., Arlington, VA, Oct. 20-23, 1991.

R. B. Poeppel, U. Balachandran, T. Suratwala, C. A. Youngdahl, J. R. Hull, and V. Dravid (Northwestern U.), Processing and Properties of Quench-Melt-Grown YBCO Superconductors, INVITED PAPER presented to 44th Pacific Coast Regional Mtg. of the Am. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

R. B. Poeppel, J. P. Singh, S. E. Dorris, J. Joo, K. C. Goretta, C.-Y. Chu, and J. L. Routbort (MSD), Processing and Mechanical Properties of High- T_c Superconductors, presented at Symp. "Conductors from High- T_c Ceram. Mater.: Theory and Fabrication" to be held at Fall Mtg. of the TMS, Cincinnati, Oct. 20-24, 1991.

R. B. Poeppel, K. C. Goretta, U. Balachandran, I. Bloom, S. E. Dorris, J. T. Dusek, J. E. Emerson, K. E. Gray (MSD), M. Hash (CTD), S. A. Johnson (CTD), R. T. Kampwirth (MSD), M. Kullberg, D. S. Kupperman, M. T. Lanagan, V. A. Maroni (CTD), R. L. McDaniel, J. H. Meiser (CTD), J. J. Picciolo, J. P. Singh, and C. A. Youngdahl, Practical Superconductor Development for Electrical Power Applications - Annual Report for FY 1990, ANL-90/47 (Oct. 1990).

R. B. Poeppel, M. T. Lanagan, U. Balachandran, S. E. Dorris, J. P. Singh, and K. C. Goretta, High-Temperature Superconductors, ASM International, Engineered Matr. Handbook, Vol. 4, Ceramics and Glasses, eds. H. F. Lampman & N. D. Wheaton (1991), pp. 1156-1160.

R. V. Raman (Ceracon, Inc.), S. V. Rele (Ceracon), U. Balachandran, and R. B. Poeppel, A Rapid Consolidation Process for Forming High Density, High Temperature Superconductors, presented at Intl. Workshop on Superconductivity, "Controlled Growth of Single- and Poly-Crystals of High Temperature Superconductors," Honolulu, June 23-26, 1992, pp. 364-365.

G. A. Risch, M. T. Lanagan, R. B. Poeppel, and M. R. De Guire (Case Western Reserve U.), Infrared-Lamp Zone Melting of the 31-A BSCCO Phase, submitted to Supercond. Sci. and Tech.

G. A. Risch (U. of Cincinnati), M. T. Lanagan, K. C. Goretta, C. A. Youngdahl, and R. B. Poeppel, Infrared Lamp Zone Refining of $\text{Bi}_2\text{Sr}_2\text{Ca}_1\text{Cu}_2\text{O}_x$, presented at Fall Mtg. of Materials Res. Soc., Boston, Dec. 2-6, 1991.

G. A. Risch, M. T. Lanagan, W. Wu, K. C. Goretta, B. M. Moon (U. of Illinois at Urbana-Champaign), $\text{YBa}_2\text{Cu}_3\text{O}_x$ Processed with a Silver/Palladium Alloy, submitted to Mater. Lett.

J. L. Routbort and K. C. Goretta, Creep of High- T_c Superconductors, INVITED ABSTRACT submitted to Symp. on "Creep, Superplasticity, Creep Fracture and Deformation Processes" to be held in conjunction with the 45th Pacific Coast Regional Mtg. of the Amer. Ceram. Soc., San Francisco, Nov. 1-4, 1992.

J. L. Routbort, K. C. Goretta, D. J. Miller, and D. B. Kazelas, Compressive Creep of Dense $\text{Bi}_2\text{Sr}_{1.7}\text{CaCu}_2\text{O}_x$, submitted to J. Mater. Res.

J. L. Routbort, N. Chen, K. C. Goretta, and S. J. Rothman, Cation and Anion Tracer Diffusion in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, INVITED KEYNOTE LECTURE ICMC '90 Topical Conf. High-Temperature Superconductors, Materials Aspects, Garmisch-Partenkirchen, West Germany, May 9-11, 1990. In Proc., eds. H. C. Freyhardt, R. Flukiger, and M. Peuckert, pp. 569-579.

R. Russell, P. S. Maiya, D. S. Poa (CT), A. S. Wagh, and R. B. Poeppel, Microstructural Characterization, Mechanical Properties, and Corrosion Resistance of the CaO-TiO_2 System, submitted to J. Mater. Res.

R. Russell, P. S. Maiya, D. Poa, A. Wagh (U. of W. Indies, Jamaica), and R. B. Poeppel, Microstructural Characterization, Mechanical Properties, and Corrosion Resistance of CaO-TiO_2 System, presented at 94th Ann. Mtg. of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

G. Selvaduray (San Jose State U.), C. Zhang (SJSU), U. Balachandran, Y. Gao (MSD), K. L. Merkle (MSD), H. Shi (MSD), and R. B. Poeppel, Effect of CO_2 on the Processing of Y-Ba-Cu-O Superconductors, J. Mater. Res., Vol. 7, No. 2, Feb. 1992, pp. 283-291

D. Shi, K. C. Goretta, J. G. Chen (U. of Illinois at Urbana-Champaign), and S. Salem-Sugui, Enhanced Flux Pinning by Crystal Defects in Melt-Textured $\text{YBa}_2\text{Cu}_3\text{O}_x$, in Proc. Symp. by Superconducting Materials Committee, The Structural Materials Div., and The Electronic Materials Div. of The Minerals, Metals and Materials Society, New Orleans, Feb. 1991, High Temperature Superconducting Compounds III, eds. S. H. Whang, A. DasGupta, and E. Collings, pp. 29-37.

D. Shi, J. G. Chen, S. Salem-Sugui, and K. C. Goretta, Critical Currents in Melt-Textured $\text{YBa}_2\text{Cu}_3\text{O}_x$, Proc. 3rd Intl. Conf. on Materials and Mechanisms of Superconductivity High-Temperature Superconductors ($\text{M}^2\text{S-HTSC}$), Kanazawa, Japan, July 22-26, 1991, Physica C 185-189 (1991) 2329-2330.

D. Shi, K. C. Goretta, S. Salem-Sugui, P. J. McGinn (U. of Notre Dame), W. H. Chen (UND), and N. Zhh (UND), Flux Creep and Pinning Potential Distribution in Zone-Melted YBaCu_3O_x , to be published in Appl. Phys. Lett. (Jan. 1991).

D. Singh and J. P. Singh, The Effect of Processing on Strength of Nicalon Fibers in Nicalon Fiber-SiC Matrix Composites, presented at 16th Ann. Conf. on Composites and Advanced Ceramics, Amer. Ceram. Soc., Cocoa Beach, FL, Jan. 7-10, 1992.

D. Singh, J. P. Singh, M. J. Wheeler, and R. T. Bhatt (NASA Lewis Research Ctr., Cleveland), Evaluation of Interfacial Shear Strength in SiC/RBSN Composites and Its Correlation to the Mechanical Properties, presented at 94th Ann. Mtg. and Exposition of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

D. Singh, J. P. Singh, M. J. Wheeler, and R. T. Bhatt (NASA Lewis Research Ctr., Cleveland), Evaluation of Interfacial Shear Strength in SiC/RBSN Composites and Its Correlation to the Mechanical Properties, Submitted to 94th Annual Mtg. and Exposition of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

D. Singh and J. P. Singh, The Effect of Processing on Strength of Nicalon Fibers in Nicalon Fiber-SiC Matrix Composites, submitted to 16th Annual Conf. on Composites and Advanced Ceramics, Amer. Ceram. Soc., Cocoa Beach, FL, Jan. 7-10, 1992.

J. P. Singh, C. Y. Chu, C. Murphy, and D. Singh, Microstructure/Mechanical-Property Relationships and R-Curve Behavior in $\text{Si}_3\text{N}_4/\text{Si}_3\text{N}_4(w)$ Composites, presented at 24th Intl. SAMPE Technical Conf., Toronto, Oct. 20-22, 1992.

J. P. Singh, R. A. Guttschow, J. T. Dusek, and R. B. Poeppel, Role of $p\text{O}_2$ in Microstructural Development and Properties of $\text{YBa}_2\text{Cu}_3\text{O}_x$ Superconductors, submitted to J. of Materials Research.

J. P. Singh, D. S. Kupperman, S. Majumdar, S. E. Dorris, N. Gopalsami, S. L. Dieckman, R. A. Jaross, D. L. Johnson, J. S. Gregar, R. B. Poeppel, A. C. Raptis, and R. A. Valentin, Sodium Heat Engine Development Program: Phase I Final Report, ANL-91/45 (Jan. 1992).

J. P. Singh, J. Joo, R. Guttschow, and R. B. Poeppel, Influence of Oxygen Partial Pressure and Silver Additions on Microstructure and Related Properties of YBCO Superconductors, INVITED PAPER presented at 1992 TCSUH Workshop on HTS Materials, Bulk Processing and Bulk Applications, Houston, Feb. 27-28, 1992.

J. P. Singh, J. Joo, R. Guttschow, and R. B. Poeppel, Influence of Microstructure on Properties of YBCO Superconductors, INVITED PAPER presented at 1992 TCSUH Workshop on HTS Materials, Bulk Processing and Bulk Applications, Feb. 27-28, 1992, Houston.

J. P. Singh, C.-Y. Chu, C. Murphy, and D. Singh, Microstructure/Mechanical Properties Relationships and R-Curve Behavior in $\text{Si}_3\text{N}_4\text{-Si}_3\text{N}_4(w)$ Composites, INVITED PAPER presented at 24th Intl. SAMPE Technical Conf., Toronto, Oct. 20-22, 1992.

J. P. Singh, D. S. Kupperman, and S. Majumdar, Strengthening of Composites by Internal Stresses: Determination by Neutron Diffraction., INVITED TALK presented at 1st Intl. Symp. on the Science of Engineering Ceramics, Koda, Japan, Oct. 21-23, 1991.

J. P. Singh, J. Joo, D. Singh, and R. B. Poeppel, Effect of Silver Addition on Microstructure and Properties of YBCO Superconductors, presented at 1992 Ann. Mtg. of Amer. Ceram. Soc., Ceram. Superconductors Symp., Minneapolis, April 12-16, 1992.

J. P. Singh, J. Joo, M. T. Lanagan, A. Grow, and R. B. Poeppel, Microstructure and Superconducting Properties of Bi-Sr-Ca-Cu-O/Ag Superconducting Tapes Made by Powder-in-Tube Technique, presented at 1992 Ann. Mtg. of Amer. Ceram. Soc., Ceram. Superconductors Symp., April 12-16, 1992, Minneapolis.

J. P. Singh, S. E. Dorris, M. T. Lanagan, C. -T. Wu, K. C. Goretti, J. Joo, U. Balachandran, and R. B. Poeppel, Processing and Properties of Superconductor Wires, submitted for publication in Proc. 4th Intl. Symp. on Superconductivity, Tokyo, Oct. 14-17, 1991.

J. P. Singh, D. S. Kupperman, and S. Majumdar, Strengthening of Composites by Internal Stresses: Determination by Neutron Diffraction, INVITED PAPER presented at 1st Intl. Symp. on Science of Engineering Ceramics, Koda, Aichi-Prefecture, Japan, Oct. 21-23, 1991.

J. P. Singh, S. Majumdar, A. S. Wagh, T. Wenzel, and R. B. Poeppel, Materials Qualification Technology for Ceramic Cross-Flow Filters, ANL/FE-91/1 (1991).

J. P. Singh, S. E. Dorris, M. T. Lanagan, K. C. Goretti, U. Balachandran, and R. B. Poeppel, Processing and Properties of Superconducting Wire, presented at 4th Intl. Symp. on Superconductivity, Tokyo, Oct. 14-17, 1991.

J. P. Singh, D. S. Kupperman, and S. Majumdar, Role of Internal Stresses in Improvement of Mechanical Properties of Ceramic Composites, INVITED PAPER presented at 44th Pacific Coast Regional Mtg. of the Amer. Ceram. Soc., San Diego, Oct. 31-Nov. 2, 1991.

J. P. Singh, R. A. Guttschow, D. S. Kupperman, J. T. Dusek, and R. B. Poeppel, Strength/Grain-Size Relationships and Internal Stresses in $\text{YBa}_2\text{Cu}_3\text{O}_x$ Superconductors, To be published in Proc. 3rd Symp. on High-Temperature Superconductors: Processing and Microstructure Property Relationships, 1991 TMS Mtg. and Exhib. New Orleans, Feb. 17-21, 1991.

S. M. Smith, J. P. Singh, and R. Scattergood (North Carolina State U.), Processing and Characterization of SiC Whisker-Reinforced Al_2O_3 Matrix, submitted for publication by Amer. Ceram. Soc.

G. W. Tomlins, A. K. Gangopadhyay, T. O. Mason (Northwestern U.), and J. P. Singh, Phase Equilibrium of Ag with Y-123 and Bi-Based Superconductors, presented at 1991 Fall Mtg. of Mater. Res. Soc., Boston, Dec. 2-6, 1991.

H. Varma (Regional Research Laboratory, India), P. Mukundan (RRL), K. Gopakurara Warriar (RRL), A. Damodaran (RRL), and U. Balachandran, Nonaqueous Cold Extrusion as a Route for Yttrium Barium Copper Oxide Wires, J. Am. Ceram. Soc. 73 (10), pp. 3100-3102.

H. K. Varma (Regional Research Laboratory, India), T. V. Mani (RRL), K. G. K. Warriar (RRL), A. D. Damodaran (RRL), and U. Balachandran, Sintering Studies on Tape Cast Alumina Substrates Derived Through Sol Spray Technique, presented at 94th Ann. Mtg. and Exposition of Am. Ceram. Soc., April 12-16, 1992, Minneapolis.

J. D. Vienna, U. Balachandran, W. Cermignani (New York State College of Ceramics), R. B. Poeppel, and J. A. Taylor (NYSCC), $\text{YBa}_2\text{Cu}_{(3-x)}\text{Co}_x\text{O}_y$ - A Substrate Material for YBCO Superconductors, presented at Materials Res. Soc. Spring Mtg., San Francisco, April 27-May 1, 1992.

J. D. Vienna, U. Balachandran, J. A. Taylor (New York State College of Ceramics), and R. B. Poeppel, $\text{YBa}_2\text{Cu}_{(3-x)}\text{Co}_x\text{O}_y$ - A Substrate Material for YBCO Superconductors, presented at Mater. Res. Soc. Spring Mtg., San Francisco, April 27-May 1, 1992.

J. D. Vienna, U. Balachandran, R. B. Poeppel, and J. A. Taylor (New York State College of Ceramics), Superconducting Coils with $\text{YBa}_2\text{Cu}_{(3-x)}\text{Co}_x\text{O}_y$ Substrate, presented at 94th Annual Mtg. of Am. Ceram. Soc., Minneapolis, April 12-16, 1992.

A. Wagh (U. of West Indies, Jamaica), D. Roberts, T. Suratwala, M. McMann, and R. B. Poeppel, Mechanical Properties of Vacuum-Sintered Yttria Ceramics, submitted to J. of Amer. Ceram. Soc. Communications.

A. S. Wagh, J. P. Singh, and R. B. Poeppel, Dependence of Ceramic Fracture Properties on Porosity, Submitted to J. of Materials Sci.

A. S. Wagh, R. B. Poeppel, and J. P. Singh, Connected-Grain Model of Electrical Conductivity of Porous Ceramics, presented at 94th Ann. Mtg. of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

K. G. K. Warriar, H. K. Varma, T. V. Mani, A. D. Damodaran (Regional Res. Lab., India), and U. Balachandran, Processing of Post-Sintered, Microwave Derived YBCO Precursor Powders, presented at 94th Ann. Mtg. and Exposition of Am. Ceram. Soc., April 12-16, 1992, Minneapolis.

B. R. Weinberger and L. Lynds (United Technologies Research Ctr.), J. R. Hull and U. Balachandran, Low Friction in High Temperature Superconductor Bearings, Appl. Phys. Lett., 59, (9), pp. 1132-1134 (1991).

C. T. Wu, K. C. Goretti, and R. B. Poeppel, Effects of Processing Parameters on Critical Current Density of Ag-Clad $\text{Bi}_2\text{CaCu}_2\text{O}_x$, submitted to Applied Superconductivity.

C. T. Wu, A. C. Blondo, K. C. Goretti, and R. B. Poeppel, Processing in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x/\text{Ag}$ Superconducting Tapes, presented at 44th Pacific Coast Regional Mtg. of Amer. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

C. T. Wu (IIT), K. C. Goretti, D. Shi (MSD), M. T. Lanagan, and R. B. Poeppel, Silver-Sheathed Multifilament Wires, Proc. 3rd Intl. Symp. on High-Temp. Superconductors: Processing and Microstructure Property Relationships, New Orleans, eds. S. H. Whang, A. DasGupta, and E. Collings, Feb. 17-21, 1991, pp. 375-383.

C.-T. Wu, A. C. Biondo, K. C. Goretti, and R. B. Poeppel, Effects of Texture and Microstructure on the Critical Current Density of Ag-Clad $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, submitted to 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

W. Wu, K. C. Goretti, and J. L. Routbort, Erosion of 2014 Al Reinforced with SiC or Al_2O_3 Particles, Mater. Sci. and Eng., A151 (1992) pp. 85-95.

W. Wu (U. of Illinois at Chicago), M. T. Lanagan, M. L. Kullberg (Amoco Chem. Co.), R. B. Poeppel, B. Wang (UIC), and S. Danyluk (UIC), The Relationship Between Microstructure and Residual Stress of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, Submitted to Thin Solid Films.

W. Wu (U. of Illinois at Chicago), M. T. Lanagan, R. B. Poeppel, and S. Danyluk (UIC), The Variability Residual Stresses of Thick Superconductor Films During Orthorhombic to Tetragonal Transformation, presented at 1992 Intl. Conf. on Advanced Science and Technology, Argonne, IL, March 28, 1992.

W. Wu (U. of Illinois at Chicago), M. T. Lanagan, R. B. Poeppel, and S. Danyluk (UIC), Relationship of Thick Film YBCO Microstructure to In-Plane Residual Stresses, presented at 94th Ann. Mtg. of Amer. Ceram. Soc., Minneapolis, April 12-16, 1992.

W. Wu (U. of I-Chi.), M. T. Lanagan, R. B. Poeppel, M. L. Kullberg (Amoco), and S. Danyluk (U of I-Chi.), Residual Stress Measurement of a $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Thick Film on Polycrystalline MgO, presented at Fall Mtg. of Materials Research Soc., Boston, Dec. 2-6, 1991.

D. H. Xu, U. Balachandran, S. E. Dorris, R. B. Poeppel, D. L. Johnson (Northwestern U.), and G. Selvaduray (San Jose State U.), Kinetic Study of Reaction of CO_2 with $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Superconductors, presented at 44th Pacific Coast Regional Mtg. of the Am. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

J. P. Zhang (Northwestern U.), F. Hanji (NU), L. D. Marks (NU), and U. Balachandran, Time and Temperature in the Decomposition of 124, presented at Fall Mtg. of Mater. Res. Soc., Dec. 2-6, 1991, Boston.

Patents

U. Balachandran and R. B. Poeppel, Thermomechanical Means to Improve the Critical Density of BSCCO Tapes. Patent application submitted July 30, 1992.

U. Balachandran and R. B. Poeppel, Low-Temperature Melt Processing of YBCO Superconductors. Patent application submitted July 6, 1992.

U. Balachandran, Diffusion Modification of Grain Boundaries of 123 Superconductor for Improved Superconductor. Patent application submitted Sept. 30, 1991.

U. Balachandran, New Insulating Substrate for 123 Superconductor. Patent application submitted Sept. 30, 1991.

U. Balachandran, Enhancement of Mechanical Properties of 123 Superconductor by Addition of BaSnO_3 . Patent application submitted Sept. 30, 1991.

U. Balachandran and C. A. Youngdahl, Improved Channeling of Magnetic Field by Superconductor. Patent application submitted July 9, 1991.

U. Balachandran, R. B. Poeppel, J. Emerson, and S. Johnson, Calcination and Solid State Reaction of Ceramic-Forming Components to Provide Single-Phase Superconducting Materials Having Fine Particle Size. U.S. Patent No. 5,086,034, awarded Feb. 4, 1992.

S. E. Dorris, K. C. Goretti, J. Creech, and R. B. Poeppel, Texturing of High T_c Superconductor under Changing Oxygen Concentration. Patent application submitted 8/6/91.

R. B. Poeppel and U. Balachandran, A Cross-Flow Reactor for Direct Conversion of Natural Gas Into High Added-Value Products. Patent application submitted June 23, 1992.

J. P. Singh, R. B. Poeppel, K. C. Goretti, and N. Chen, Formation of Complex Oxide Ceramics with Improved Physical and Mechanical Properties. Patent application submitted Oct. 4, 1991.

J. P. Singh, R. A. Guttschow, J. T. Dusek, and R. B. Poeppel, Improved Microstructure and Properties of YBCO Sintered at Reduced $p\text{O}_2$. Patent application submitted 8/14/91.

Corrosion

Section Manager: T. F. Kassner

Principal Investigators: O. K. Chopra, H. M. Chung, A. B. Hull, B. A. Loomis,

K. Natesan, J. H. Park, W. E. Ruther

Support Staff: A. Sather,¹ W. K. Soppet

Technicians: R. W. Clark, G. M. Dragel, L. J. Nowicki, D. L. Rink

Secretary: S. M. Hagamann²

Visiting Professor: J. A. Todd³

Resident Associate: M. Satou⁴

Students: L. Y. Bush,⁵ F. Ceale,⁶ M. R. Fox,⁷ D. M. French,⁸ J. Gazda,⁹ M. L. Y. Herrero,¹⁰

P. R. Luebbers,¹¹ W. F. Michaud,⁹ I. M. Purdy²

Programs of the Corrosion Section address specific concerns related to corrosion and the effect of various environments on mechanical behavior of materials used in several types of energy systems. The research is sponsored by various divisions of the Department of Energy and the Nuclear Regulatory Commission. Research on aqueous, gaseous, and liquid-metal corrosion, thermodynamics and kinetics of gas-solid reactions, and high-temperature mechanical properties in three major program areas is summarized below.

Light-Water Reactors

Environmentally assisted cracking of piping, in-core components, and pressure vessels in light-water reactors (LWRs) is an important concern as extended reactor lifetimes are envisaged. Cracking of weld-sensitized Type 304 SS piping in boiling water reactors (BWRs) has been mitigated largely by hydrogen-water chemistry and improved water purity. However, cracks that initiate in sensitized SS safe ends and SS cladding have propagated into low-alloy ferritic steel nozzles and pressure vessels, and extensive cracking has occurred in upper shell-to-transition-cone girth welds in nonclad pressurized water reactor (PWR) steam generator vessels. Incidents of cracking of nonsensitized SS in BWR and PWR core-internal components have become more frequent as the plants age and fast-neutron fluence increases. As part of an NRC-sponsored program on environmentally assisted cracking in LWR systems, we are evaluating the effect of simulated BWR and secondary-side PWR water on the stress corrosion cracking (SCC) of austenitic stainless and low-alloy ferritic steels. Factors that contribute to irradiation-assisted stress corrosion cracking (IASCC) of commercial- and high-purity austenitic SS are also being investigated.

¹ Special Term Appointee.

² Serves two sections.

³ Illinois Institute of Technology.

⁴ Tohoku University, Japan.

⁵ University of Cincinnati.

⁶ Grenoble, France.

⁷ Purdue University.

⁸ Rensselaer Polytechnic Institute.

⁹ University of Illinois at Chicago.

¹⁰ Polytechnic Institute, Mexico City.

¹¹ University of Illinois at Urbana-Champaign.

Stress Corrosion Cracking of Austenitic Stainless in Simulated BWR Coolant Environments

Current BWR operating practices have reduced to very low levels the ingress of ionic impurities (e.g., sulfate, chloride) into the coolant system. Soluble corrosion products, viz., chromate and the counterbalancing hydronium ion, are now the major ionic species present. Because only a small fraction of the recirculation water in BWRs passes through the reactor water cleanup system, the concentration of chromate ions in the reactor water can be much greater than in the feedwater (e.g., $\approx 25\text{--}35$ ppb versus <1 ppb, respectively). Possible synergistic reactions involving chromate and sulfate in SCC of sensitized Type 304 SS were investigated by fracture-mechanics CGR tests. The results in the figure below indicate that the CGRs of sensitized Type 304 SS under high-R, low-frequency loading are low ($<4 \times 10^{-11} \text{ m}\cdot\text{s}^{-1}$ or $<1 \text{ mm}\cdot\text{yr}^{-1}$), provided that the chromate/sulfate concentration ratio in oxygenated feedwater is >3 . Thus, a low chromate concentration in BWR water (25–35 ppb) may actually have a beneficial effect on SCC, provided that the sulfate concentration is below a critical level (i.e., ≈ 10 ppb).

Stress Corrosion Cracking of Ferritic Steels in Simulated Coolant Environments

Crack-growth-rate (CGR) tests have continued on fracture-mechanics-type specimens of A533-Gr B steel under high-load-ratio, low-frequency loading conditions at 289°C . In

Regime of high and low CGRs for moderately sensitized (EPR = $8 \text{ C}\cdot\text{cm}^{-2}$) Type 304 SS specimen at 289°C as a function of ratio of chromate and sulfate concentrations in feed water containing ≈ 300 ppb dissolved oxygen

contrast to specimens clad with Inconel-182 weld metal and plated with nickel, it is relatively difficult to crack nonplated specimens under the same loading conditions. Whereas cracking of the underlying A533-Gr B steel can be initiated by triggering events in the environment (e.g., increases in dissolved-oxygen concentration) and/or in the loading conditions (increases in K_{max} or decreases in load ratio), fatigue cracks in the nonplated specimens tend to become plugged with corrosion product, and resumption of crack growth is difficult to achieve in most cases. The rationale for this type of behavior has not been established; however, it appears that general corrosion of low-alloy steel specimens in simulated BWR water is high enough to suppress macrocell corrosion at the crack tip, which facilitates SCC of austenitic SS and plated or weld-clad ferritic steel specimens. The ongoing investigation of this phenomenon will focus on simulated PWR secondary-side environments where pH is higher, and consequently, the general corrosion rate and solubility of corrosion products in the water are much lower. These conditions would tend to focus corrosion at the crack tip.

Irradiation-Induced Stress Corrosion Cracking of Austenitic Stainless in Simulated BWR Water

Radiation-induced segregation (RIS) of alloying and impurity elements in austenitic steels irradiated to high-fluence in BWRs and PWRs is being investigated by scanning Auger microscopy to determine its role in IASCC of the steels. Additional work has confirmed that the extent of chromium depletion near a grain boundary in high-purity (HP) Type 304 SS is considerably higher than that in commercial-purity (CP) steels irradiated to the same fluence. Slow-strain-rate-tensile (SSRT) tests on specimens of the CP and HP heats of Type 304 SS in simulated BWR water have shown that at a comparable fluence level, the HP material exhibits greater SCC susceptibility. It is difficult to explain the significant IG fracture in HP absorber-tube specimens on the basis of Si or P segregation because impurity segregation in the HP heat was negligible. Likewise, it is difficult to correlate negligible SCC susceptibility of the CP absorber-tube sheath and absorber-tube specimens to significant Si or P segregation. Therefore, it seems evident that grain-boundary segregation of Si or P is not the mechanism of IASCC, as has been speculated up to now. Rather, the results of SSRT tests of the CP and HP components seem to be consistent with a mechanism in which irradiation-induced Cr depletion is the primary process, at least in simulated BWR water. This is shown in the next figure, where percent IGSCC in SSRT specimens is plotted as a function of the minimum grain-boundary Cr levels, based on Auger electron spectroscopy (AES) analyses of specimens from one HP and two CP heats of BWR-irradiated Type 304 SS material.

To further investigate the effects of alloy composition, fast-neutron dose rate, and fluence on IASCC of austenitic SS, SSRT and miniaturized compact-tension fracture-toughness specimens were fabricated from 27 heats (compositional variations of Types 304, 316, and 348 SS) for irradiation in the OECD Halden Reactor, a heavy-boiling-water reactor (HBWR). Compositions of the heats are based on a Taguchi matrix (i.e., a matrix that minimizes the number of test specimens) designed to separate the effects of Ni, Si, P, S, Mn, C, N, and Cr on IASCC susceptibility.

Percent IGSCC from SSRT tests vs. minimum grain-boundary Cr content from AES analysis of HP and CP Type 304 SS BWR components

Long-Term Embrittlement of Cast Duplex Stainless Steels

Cast stainless steels used in LWR systems for primary pressure-boundary components such as valve bodies, pump casings, and primary coolant piping undergo substantial reductions in fracture toughness after extended service at reactor operating temperatures. Mechanical-property tests (Charpy-impact, tensile, and static fracture-toughness J-R curve) were completed on materials that were aged in the laboratory for up to 50,000 h and on materials obtained from two decommissioned reactors. The microstructures of the aged materials were characterized by high-voltage transmission electron microscopy (HVEM), small-angle neutron scattering (SANS), and field-ion atom probe (FIAP) techniques to identify the mechanism of embrittlement and validate the simulation of in-reactor degradation by accelerated-aging studies. The precipitation of additional phases in the ferrite matrix, e.g., a Cr-rich α' phase that forms by spinodal decomposition and an Ni- and Si-rich G phase, and precipitation and/or growth of carbides and nitrides at the ferrite/austenite phase boundaries are the primary cause for embrittlement of cast stainless steels. In general, the results indicated that low-carbon CF-3 grades of cast stainless steels are the most resistant to low-temperature embrittlement, and that Mo-containing, high-carbon CF-8M grades are the most susceptible. A methodology and correlations were developed for predicting the fracture toughness J-R curves and impact strength of cast components of known composition as a function of time and temperature during reactor service. Our work provides a technical basis for an assessment of toughness loss for leak-before-break analyses of coolant-pressure boundaries, and insight into whether thermal aging of the steels will be a limiting factor in extension of nuclear-plant life beyond ≈ 40 years. Crack-growth-rate tests are being conducted on specimens of long-term aged CF-8 and CF-8M SS that exhibited large losses in toughness to determine if microstructural changes in these materials can also promote SCC in simulated reactor coolant environments.

Fossil Energy

Studies of the high-temperature corrosion of metallic materials are being conducted in simulated coal-gasification, fluidized-bed-combustion, and magnetohydrodynamic (MHD) power generation environments to establish mechanisms of corrosion, predict the onset of breakaway corrosion, and evaluate the role of stress and deformation in the corrosion process. The sulfidation resistance of structural alloys; model Fe-Cr, Fe-Cr-Ni, and Fe-Cr-Al alloys with controlled additions of several refractory metals and rare earth elements; and oxide-dispersion-strengthened alloys is being evaluated by thermogravimetric tests and postexposure microstructural characterization of corrosion scales by several electron-optical microscope techniques. Alloy additions are made by bulk alloying, ion implantation, sputter deposit/ion-beam mixing, and as coatings. In-situ electrochemical measurements on thermally grown oxide scales yield information on the ionic transport properties of the layers.

Corrosion Behavior in Coal Conversion and MHD Power Generation Systems

In gasification and in the first stage of MHD combustor environments, the gas chemistry is such that oxygen partial pressures are relatively low and sulfur partial pressures are moderate-to-high, depending on sulfur content of the coal feedstock. In such environments, structural materials are subjected to sulfidation attack and catastrophic corrosion, especially at elevated temperatures. Because the major objective in the development of corrosion-resistant alloys is to form a scale that is slow-growing and well bonded to the substrate alloy, research is underway to modify the surface regions of the alloy in order to enhance nucleation-growth of the oxide scale in the early stages of alloy exposure. Coatings have been developed via pack cementation and electrospark deposition (ESD) techniques and were examined for their corrosion resistance in sulfur-containing atmospheres. Test programs were conducted to evaluate the sulfur resistance of coatings, determine the influence of coating technique on corrosion, and compare the corrosion rates of coated and uncoated structural alloys in simulated gasification atmospheres. The figure on the next page shows a comparison of corrosion-loss data obtained for a low-alloy steel (T22) in the uncoated condition and for several different coatings after exposure to a high-sulfur environment at 500 and 650°C. The results show substantial improvement for the pack cementation coatings and the ESD Cr carbide/Al coating in these reducing environments. Research is in progress to develop oxide-dispersion-strengthened bulk alloys and to modify surfaces of several engineering alloys to improve their corrosion resistance in environments typical of coal-fired systems.

Corrosion Behavior in Combustion Power Generation Systems

In support of fluidized-bed combustion (FBC) materials development, extensive testing of candidate materials has been conducted in simulated combustion environments in laboratory test facilities and in a 1.8-m x 1.8-m advanced fluidized-bed combustion unit at the Rockwell International Energy Technology Engineering Center (ETEC) in El Segundo, CA. The laboratory tests examined the role of gas chemistry, sulfur sorbent, metal temperature, and cycling of gas chemistry on the corrosion of heat exchanger and tube

support materials in FBC systems. The results showed that deposits of sulfated sorbent alone can lead to sulfidation of low-alloy steels. The austenitic alloys developed (Ca,Cr) oxide and/or chromia scales at steam temperatures but exhibited significant intergranular sulfidation at air-heater temperatures. The gas-cycling experiments showed that sulfidation can be triggered even in Type 310 SS (normally resistant to sulfidation attack) with a cycle time of 100 h in which the gas chemistry varied between oxidizing and sulfidizing every 100 h. A comparison of data obtained in the presence of reagent-grade CaSO_4 (simulating deposits in a bubbling FBC) and circulating fluid-bed (CFB) ash deposits showed acceptable corrosion behavior for a number of high-chromium austenitic alloys in CFB atmospheres, and to a limited extent in bubbling-bed conditions.

In addition to laboratory test data, we conducted detailed microstructural analyses on specimens exposed in uncooled and cooled probes from ANL, B&W, and FW after exposure in the Rockwell International FBC system. Penetration depths were measured for several of the materials as a function of specimen orientation, exposure location in the combustor, and time of location. These results, together with the laboratory test data, were used to determine the role of key variables that contribute to accelerated corrosion of materials and to assess the long-time performance of candidate materials for air-heater applications. The figure on the next page shows corrosion rates calculated for several candidate alloys exposed in laboratory studies (tests A2 and C), as well as in ETEC FBC tests. The data included in this figure incorporate information developed at ANL from all specimens (from ANL, B&W, and FW probes). The ETEC test data in this figure are differentiated as to whether or not the specimens were covered with the bed material. The data show that some of the alloys (such as 800H, HK 40, HS 188, and HS 556) are susceptible to catastrophic corrosion when subjected to a sustained low- $p\text{O}_2$ and relatively high- $p\text{S}_2$ environment (dictated by the boundary between CaO and CaSO_4 phases).

Corrosion loss data for T22 alloy in the uncoated condition and with several coatings after 2000 hr (unless marked otherwise) exposure to high-sulfur gas atmosphere at 500 and 650°C

Corrosion rates for several structural materials for application in FBC systems

The next worst environment from the materials corrosion standpoint is one in which bed deposit material is present. Of the alloys exposed to a bed deposit in the ETEC exposure, HP 50 and Sanicro 33 exhibited 4- to 6-mm·yr⁻¹ corrosion, while 253 MA, HS 556, HS 188, XM 19, and HK 40 exhibited ≈2 mm·yr⁻¹ corrosion rate. It should be noted that FBC systems will probably not experience a sustained low-pO₂ atmosphere for thousands of hours; the materials corrosion data obtained in Test A2 may be overly pessimistic, and selection of materials based on this test data will be overly conservative. The gas-cycling data showed that the alloys, in general, can tolerate the oxidizing/reducing environments as long as the alloys are exposed to oxidizing condition in the startup cycle. Only HS 188 exhibited high corrosion, which was manifested as internal oxidation of the alloy. The results show that a number of structural alloys and some of the chromized coatings performed well under all environmental conditions used in the different tests. The corrosion rates for these materials were in the range of 0.25–0.40 mm·yr⁻¹ for temperatures in the range of 775–871°C. In the case of air tubes with 5–6 mm wall thickness, the above corrosion rates will lead to a thickness loss of 0.8–1.25 mm after 10 years of service in the FBC environment.

Fusion Energy

Structural materials in a fusion reactor will be cooled by either an aqueous or liquid-metal coolant while undergoing displacement damage and transmutation reactions that produce hydrogen and helium atoms within the materials due to 14-MeV-neutron irradiation. Austenitic SSs, ferritic steels, and niobium- and vanadium-base alloys are likely

candidates for the first wall and divertor in the International Thermonuclear Experimental Reactor (ITER) and in subsequent power-producing fusion reactors. Current research is directed toward the acquisition of material-property data for design and construction of ITER and subsequent reactors. Studies include aqueous SCC of austenitic SSs in oxygenated water, aqueous corrosion and embrittlement of niobium-base alloys for divertor applications, corrosion of vanadium-base alloys in liquid lithium, and evaluations of the tensile, creep, fracture-toughness, and swelling properties of vanadium-base alloys after fast-neutron irradiation in Hanford Engineering Development Laboratory's Fast-Flux Test Facility at 420 and 600°C.

Effects of Simulated Fusion Reactor Environments on Corrosion and Stress Corrosion Cracking of Candidate Structural Materials

Susceptibility of Types 316NG and sensitized 304 SS to SCC was investigated at temperatures of 60–289°C in SSRT tests in oxygenated water that simulates important parameters anticipated in first-wall/blanket systems. Because small differences in the load-versus-elongation behavior of specimens in air and in water at small plastic strains were not reliable enough to quantify SCC susceptibility of resistant materials, SSRT tests were conducted to failure in this investigation. Total elongation at failure appears to be the most promising measure of SCC susceptibility. Consequently, the data were analyzed on the basis of a strain-ratio parameter, namely, $S_r = \epsilon_{env}/\epsilon_{air}$ at failure for identical specimen geometries (crevice or noncrevice). Strain-ratio values for different heats of Type 316NG SS and our reference heat of Type 304 SS for several levels of sensitization are plotted as a function of temperature in the next figure (below). The results show that both steels are resistant to SCC in oxygenated water containing ≈ 0.1 ppm sulfate at temperatures $\leq 150^\circ\text{C}$, i.e., the S_r values are ≈ 1.0 . At higher temperatures, the S_r values decrease significantly, indicating SCC. Below $\leq 100^\circ\text{C}$, noncrevice specimens of Type 316NG SS appear to exhibit greater SCC susceptibility than do crevice specimens, which is difficult to explain when compared with behavior at high temperatures. In almost all tests on crevice specimens, fracture occurred in the hole that contained the pin; we attribute this to the more aggressive crevice water chemistry, although noncrevice specimens actually have lower S_r values, at least at lower temperatures. Type 316NG SS exhibits good resistance to SCC under crevice and noncrevice conditions at temperatures $< 150^\circ\text{C}$ in nominal ITER coolant chemistry that does not contain any short-lived radical species from radiolysis of water. SSRT tests on crevice-type weldment specimens of Type 316NG SS are being conducted under nominal and off-normal water chemistries at several temperatures.

Effect of Alloy Composition and Hydrogen Content on Ductile–Brittle Transition Temperature of Irradiated Vanadium–Base Alloys

Vanadium-base alloys are attractive for structural materials in fusion reactors because of their good mechanical, corrosion, and irradiation performance. However, some alloys exhibit high ($> 250^\circ\text{C}$) ductile–brittle–transition temperatures (DBTT), which would make them unacceptable. To address this issue, miniature Charpy–impact specimens of V–Cr–Ti and V–Ti–Si alloys containing < 30 and 400 – 1200 appm H were prepared and Charpy tests were conducted at temperatures between -190 and 250°C . A curve for the energy absorbed

Strain ratio at failure for crevice and noncrevice SSRT specimens of Types 316NG and sensitized 304 SS in oxygenated water versus temperature

Dependence of DBTT on Ti and Cr concentration in vanadium-base alloys containing <30 and 400-1200 appm H

during impact versus test temperature was fitted with a hyperbolic tangent equation to determine the inflection point, which was used to define the DBTT. The effect of Ti and Cr concentration on the DBTT of V, V-Ti, and V-Cr-5Ti alloys containing low and moderate H contents is shown in the figure above. The results show that when the combined Cr and Ti concentration is $\approx 5\%$, the DBTT is minimal, i.e., ≈ -250 and -160°C for alloys containing <30 and 400-1200 appm H. On the basis of present results and tensile properties, the V-5%Cr-5%Ti alloy appears to be the most promising candidate.

Effects of Irradiation-Induced Precipitation on Properties of Vanadium Alloys

The microstructures and properties of vanadium-base alloys are profoundly modified during neutron irradiation. Transmission electron microscopy evaluations were performed on the irradiated and nonirradiated alloys to interpret mechanical-property information and to optimize a structural alloy for fusion reactor designs. The major precipitates that form in these materials are Ti_5Si_3 and Ti_2O . Precipitation of very fine Ti_5Si_3 particles at 420°C increases monotonically with increasing neutron dose to ≈ 120 dpa, whereas at 600°C , maximum precipitation occurs at ≈ 20 – 40 dpa. The precipitation characteristics were correlated with swelling and elongation behavior of the alloys. For operation at 420°C , it is important to optimize the Si level in the alloy and ensure that there is sufficient Ti "in solution," to optimize Ti_5Si_3 precipitation (a high number density) which provides resistance to void swelling. At 600°C , minimizing the O content, in addition to Si and Ti control, is important to minimize Ti_2O precipitation, which reduces ductility. For structural applications in a fusion reactor, it is desirable to minimize Ti_2O precipitation while maintaining an optimal level of Ti_5Si_3 precipitation in vanadium-base alloys.

Development of Electrical Insulator Coatings for Liquid-Metal Blanket Applications

Magnetohydrodynamic (MHD) forces and their effects on corrosion, heat transfer, and pressure drop are a key concern with a V-alloy/Li system for first-wall applications in a magnetic fusion reactor. MHD effects could be reduced significantly by placing an electrical insulator coating at the V-alloy/Li interface. For a material to work as an insulator coating in this environment, it must meet two criteria: high corrosion resistance and electrical resistivity $> 10^2 \Omega\cdot\text{m}$ when exposed to Li and a radiation field. Corrosion tests have been conducted on candidate coating/substrate combinations in liquid Li. The coating materials selected on the basis of chemical stability include BN, Y_2O_3 , Cr_2O_3 , MgO, CaO, Si_3N_4 , V_2O_5 , and in-situ coatings of calcium vanadate and a V-Ti-N reaction-product layer formed on V-20Ti in flowing Li. Yttrium oxide exhibited excellent corrosion resistance in flowing liquid Li at 400°C . Electrical resistivity measurements by a standard four-probe method on Y_2O_3 in air at temperatures between ≈ 450 and 1000°C , before and after exposure to Li for 675 h at 410°C , indicated no deterioration in resistivity, as shown in the final figure. The resistivity of in-situ-formed $(\text{V,Ti})_x\text{N}$ reaction-product layers on V-20Ti during exposure to Li for 1384 h at 538°C and TiN on Ti was determined at room temperature and 80°C by a two-probe method. The resistivity of the film on the V-20Ti alloy was low ($\approx 20 \Omega\cdot\text{m}$) and the film on Ti exhibited metallic conduction.

Adhesion bonding between Y_2O_3 and Y, V, Ti, V-20Ti, V-3Ti-1Si, and Types 304 and 316 SS was also investigated in reducing ($3\%\text{H}_2\text{-N}_2$) and oxidizing ($50 \text{ ppm O}_2\text{-N}_2$) gaseous environments at 927°C . Except for the V-20Ti alloy, the V-base alloys, Ti, and Type 304 SS were well-bonded to Y_2O_3 in a reducing atmosphere. In an oxidizing atmosphere, bond regions of Types 304 and 316 SS were better than in a reducing atmosphere because of reaction between the oxide scale on the steels (Cr_2O_3) and Y_2O_3 to form YCrO_3 . Neither V, Ti, nor the V alloys bonded with Y_2O_3 . These results suggest that a low-melting eutectic layer forms between Y_2O_3 and the oxides layers present on V, Ti, and the V-alloys at high temperatures.

In ongoing work, the feasibility of producing in-situ coatings of Ca, Si, Al, and Y on V and V-alloys by dissolution of these elements in Li is being investigated. Yttrium coatings on V and V-alloys are being prepared, and Y will be oxidized to Y_2O_3 before exposure to Li. Similarly, $(V,Ti)_xN$ layers on V-Cr-Ti and V-Ti alloys will be fabricated and exposed to Li to determine their chemical stability. In-situ methods are being explored for measuring electrical properties of insulator coatings in Li.

Electrical resistivity of Y_2O_3 in air before and after exposure to Li at 410°C for 675 h

Recent Work by the Corrosion Section

Publications

O. K. Chopra, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems, Semiannual Report: Oct. 1990-March 1991, NUREG/CR-4744, Vol. 6, No. 1, ANL-91/22 (1991).

O. K. Chopra, Prediction of Aging Degradation of Cast Stainless Steel Components in LWR Systems, INVITED PAPER presented at NRC Aging Research Information Conf., March 24-27, 1992, Rockville, MD.

O. K. Chopra and W. J. Shack, Evaluation of Aging Degradation of Structural Components, INVITED PAPER presented at NRC Aging Research Information Conf., March 24-27, 1992, Rockville, MD.

O. K. Chopra, Thermal Aging of Cast Stainless Steels in LWR Systems: Estimation of Mechanical Properties, presented at Nucl. Plant Systems/Components Aging Management and Life Extension, 1992 ASME Pressure Vessel and Piping Conf., New Orleans, June 1992.

O. K. Chopra, Mechanical Property Degradation of Cast Stainless Steel Components from Shippingport Reactor, INVITED PAPER presented 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Bethesda, MD, NUREG/CP-0119, Vol. 1, pp. 179-195.

O. K. Chopra, Estimation of Mechanical Properties of Cast Stainless Steels during Thermal Aging in LWR Systems, INVITED PAPER presented at 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Bethesda, MD, NUREG/CP-0119, Vol. 1, pp. 151-178.

O. K. Chopra, Estimation of Mechanical Properties of Cast Stainless Steels during Thermal Aging in LWR Systems, for publication in Nuclear Eng. and Design.

O. K. Chopra, Studies of Aged Cast Stainless Steel from the Shippingport Reactor, to be published in Nucl. Engr. and Design.

O. K. Chopra, W. J. Shack, and S. T. Rosinski (Sandia National Laboratories), Radiation Embrittlement of the Neutron Shield Tank from the Shippingport Reactor, NUREG/CR-5748, ANL-91/23, SAND91-1933 (Sept. 1991).

O. K. Chopra, Estimation of the Change in Fracture Toughness of Cast Stainless Steels Due to Thermal Aging in LWR Systems, NUREG/CR-4513, ANL-90/42 (1991).

O. K. Chopra and H. M. Chung, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems - Semiannual Report Oct. 1987-March 1988, NUREG/CR-4744, ANL-89/22, Vol. 3 (1989).

O. K. Chopra, A. Sather, and L. Y. Bush, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems, NUREG/CR-4744, Vol. 4, No. 2, ANL-90/49 (1990).

O. K. Chopra, Estimation of Fracture Toughness of Cast Stainless Steels during Thermal Aging in LWR Systems, NUREG/CR-4513, ANL-90/42 (June 1991).

O. K. Chopra, Thermal Aging of Cast Stainless Steels in LWR Systems: Estimation of Mechanical Properties, presented at Nuclear Plant Systems/Components Aging Management and Life Extension, 1992 ASME Pressure Vessel and Piping Conference, New Orleans.

O. K. Chopra and L. Y. Bush, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems: Semiannual Report Oct. 1989-March 1990, NUREG/CR-4744, Vol. 5, No. 1, ANL-91/7 (1991).

O. K. Chopra, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems: Semiannual Report April-September 1990, NUREG/CR-4744, Vol. 5, No. 2, Category R5, ANL-91/10 (1991).

O. K. Chopra, A. Sather, and L. Y. Bush, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems - Semiannual Report, April-September 1989, NUREG/CR-4744, Vol. 4, No. 2, ANL-90/49 (1990).

O. K. Chopra and H. M. Chung, Long-Term Embrittlement of Cast Duplex Stainless Steels in LWR Systems, to be published by Office of Nuclear Regulatory Research, U.S. Nuclear Regulatory Commission as NRC Ann. Report for FY 1990.

O. K. Chopra, H. M. Chung, and W. J. Shack, Materials Studies on Service-Aged Components, To be published in Compilation of Contract Research for the Materials Engineering Branch, Div. of Engineering: Ann. Report for FY 1990 by Office of Nuclear Regulatory Research, U.S. Nuclear Regulatory Commission.

O. K. Chopra and H. M. Chung, Long-Term Embrittlement of Cast Stainless Steels in LWR Systems - Semiannual Report Oct. 1988-March 1989, NUREG/CR-4744, Vol. 4, No. 1, ANL-90/44 (1991).

H. M. Chung, Effects of Irradiation-Induced Precipitation on Properties of Vanadium Alloys, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

H. M. Chung, J. E. Sanecki, W. E. Ruther, and T. F. Kassner, Irradiation-Induced Modification of Grain-Boundary Microchemistry in Stainless Steels, to be presented to Symp. on Microstructures and Mechanical Properties of Aging Materials, TMS-AIME Fall Mtg., Nov. 1-5, 1992, Chicago.

H. M. Chung and D. L. Smith (FPP), Irradiation-Induced Precipitation in Vanadium-Base Alloys Containing Titanium, submitted to 16th Intl. Symp. on Effects of Radiation on Materials, June 21-25, 1992, Denver.

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Stress Corrosion Cracking Susceptibility of Irradiated Type 304 Stainless Steels, presented to 16th Intl. Symp. on Effects of Radiation on Materials, June 21-25, 1992, Denver.

H. M. Chung, L. J. Nowicki, and D. L. Smith (FPP), Irradiation-Induced Precipitates in Vanadium Alloys Containing Titanium, Contribution to Fusion Reactor Materials Semiannual Progress Report for the Period Ending Sept. 30, 1991 (Published by ORNL).

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Irradiation-Induced Sensitization and Stress Corrosion Cracking of Type 304 Stainless Steel Core-Internal Components, presented at 5th Intl. Symp. on Degradation of Materials in Nuclear Power Systems - Water Reactors, Aug. 25-29, 1991, Monterey, CA.

H. M. Chung and D. L. Smith (FPP), Correlation of Microstructure and Tensile and Swelling Behavior of Neutron-Irradiated Vanadium Alloys, presented at 5th Intl. Conf. on Fusion Reactor Materials, Nov. 17-22, 1991, Clearwater, FL.

H. M. Chung, B. A. Loomis, D. L. Smith, and K. Abe, Correlation of Microstructure and Swelling Behavior of Vanadium Alloys Irradiated in FFTF/MOTA at 420°C, Contribution to Fusion Reactor Materials Semiannual Progress Report for the Period Ending March 30, 1991, DOE-ER/0313/10; published by ORNL.

H. M. Chung, B. A. Loomis, and D. L. Smith (FPP), Correlation of Microstructure and Tensile and Swelling Behavior of Neutron-Irradiated Vanadium Alloys, submitted to 5th Intl. Conf. on Fusion Reactor Mat., Nov. 17-22, 1991, Clearwater, FL.

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Understanding Susceptibility of In-Core Components to Irradiation-Assisted Stress Corrosion Cracking, submitted to Amer. Nucl. Soc. Intl. Top. Mtg. on Safety of Thermal Reactors, July 21-25, 1991, Portland, OR.

H. M. Chung, Aging and Life Prediction of Cast Duplex Stainless Steel Components, INVITED PAPER: Int. J. Pres. Ves. & Piping 50 (1992) pp. 179-213. (Proc. ASME Pressure Vessel and Piping Conf., June 23-27, 1991, San Diego).

H. M. Chung, T. F. Kassner, J. Y. Park, W. E. Ruther, J. E. Sanecki, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors (condensed version), to be published in Compilation of Contract Research for the Materials Engineering Branch Division of Engineering Annual Report for FY 1990, NUREG-0975, Vol. 8.

H. M. Chung, T. F. Kassner, W. J. Shack, W. E. Ruther, J. Y. Park, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-Sept. 90, NUREG/CR-4667 Vol. 11, ANL-91/9 (1991).

H. M. Chung and O. K. Chopra, Characterization of Duplex Stainless Steels by TEM, SANS, and APFIM Techniques, INVITED PAPER: Proc. Intl. Metallographic Society Symp. on Characterization of Advanced Materials, Monterey, CA, July 27-28, 1987, eds. W. Altergott and E. Henneke, Plenum Press, New York and London (1991), pp. 123-147.

M. R. Fox, A. B. Hull, J.-H. Park, J.-H. Hsieh, and G. Dragel, Corrosion and Electrical Properties of Ceramic Insulators after Exposure to Flowing Lithium at 400°C, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1991, Report No. DOE-ER/0313/10; published by ORNL.

A. B. Hull, P. R. Luebbers, M. R. Fox, W. K. Soppet, and T. F. Kassner, Aqueous Stress Corrosion of Candidate Austenitic Steels for ITER Structural Applications, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

A. B. Hull, M. R. Fox, and J.-H. Hsieh, Vanadium-Base-Alloy Surface Modification for Liquid Metal Blankets and First-Wall in Magnetic Fusion Reactors, presented at 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

A. B. Hull, B. A. Loomis, and L. J. Nowicki, Preliminary Assessment of Aqueous Corrosion of Niobium Alloys for Structural Applications in the ITER Divertor, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1991, Report No. DOE-ER/0313/10; published by ORNL.

A. B. Hull and T. F. Kassner, Aqueous Stress Corrosion of Candidate Austenitic Steels for ITER Structural Applications: The Role of Hydrogen, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1991, Report No. DOE-ER/0313/10; published by ORNL.

A. B. Hull, T. F. Kassner, and M. R. Fox, Stress Corrosion Susceptibility of Austenitic Stainless Steels, Including Weldments, in Oxygenated Water, submitted to 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

A. B. Hull and B. A. Loomis, Assessment of Niobium-Base-Alloy Chemical Compatibility and Mechanical and Physical Characteristics for Structural Application in the ITER Divertor, submitted for presentation at 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

A. B. Hull, O. K. Chopra, B. Loomis, and D. Smith (FPP), Compatibility between Vanadium-Base Alloys and Flowing Lithium: Partitioning of Hydrogen at Elevated Temperatures, J. Nucl. Mater. 179-181, 824-826 (1991). (Proc. 4th Intl. Conf. on Fusion Reactor Materials, Kyoto, Japan, Dec. 4-8, 1989.)

Y. H. Jeong and K. S. Rheem (KAERI), and H. M. Chung, Characteristics of Autoclave and In-Reactor Nodular Corrosion of Zircalloys, presented at 9th Intl. Symp. on Zirconium in the Nuclear Industry, Nov. 5-8, 1990, Kobe, Japan.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, presented at NRC Aging Res. Info. Conf., March 24-27, 1992, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, W. K. Soppet, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-September 1991, NUREG/CR-4667, Vol. 13, ANL-92/6 (1992).

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, INVITED PAPER presented at 19th Water Reactor Safety Information Mtg., Rockville, MD, Oct. 28-30, 1991.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, W. K. Soppet, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors Semiannual Report April-September 1991, NUREG/CR-4667, Vol. 13 (1992).

T. F. Kassner, J. Y. Park, W. E. Ruther, W. J. Shack, D. R. Diercks, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors, Semiannual Report Oct. 1988-March 1989, NUREG/CR-4667, ANL-90/4, Vol. 8 (1990).

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, presented at 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, Proc. 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Bethesda, MD, NUREG/CP-0119, Vol. 1, pp. 127-150.

T. F. Kassner, J. Y. Park, W. E. Ruther, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-Sept. 1989, NUREG/CR-4667 Vol. 9, ANL-90/48 (1991).

B. A. Loomis, D. L. Smith, H. Matsui (Tohoku U., Japan), M. L. Hamilton (PNL, Japan), K. L. Pearce (Westinghouse Hanford Co.), J. P. Kopasz, C. E. Johnson, R. G. Clemmer, and L. R. Greenwood (PNL), Status of the Dynamic Helium Charging Experiment (DHCE), Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

B. A. Loomis, C. F. Konicek, L. J. Nowicki, and D. L. Smith, Tensile Properties of Vanadium-Base Alloys with a Tungsten-Inert-Gas Weld Zone, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12

B. A. Loomis, C. F. Konicek, L. J. Nowicki, and D. L. Smith (FPP), Tensile Properties of Vanadium-Base Alloys with a Tungsten-Inert-Gas Weld Zone, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

B. A. Loomis and D. L. Smith, Vanadium Alloys for Structural Applications in Fusion Systems: A Review of Vanadium Alloy Mechanical and Physical Properties, for inclusion in Proceedings 5th Intl. Conf. on Fusion Reactor Mater., Nov. 17-22, 1991, Clearwater, FL.

B. A. Loomis and D. L. Smith (FPP), Swelling of Neutron-Irradiated Vanadium-Base Alloys, to be published in Proc. 16th Symp. on Effects of Radiation on Materials, June 21-25, 1992, Denver.

B. A. Loomis, L. J. Nowicki, and D. L. Smith, The Effect of Hydrogen, Chromium, Titanium, and Silicon on the Ductile-Brittle Transition Temperature of Vanadium and Vanadium-Base Alloys, Contribution to: Fusion Reactor Materials Semiannual Progress Report for Period Ending Sept. 30, 1991 - Report No. DOE-0313/11.

B. A. Loomis, A. B. Hull, and D. L. Smith (FPP), Vanadium Alloys for Structural Applications in Fusion Systems, presented at 5th Intl. Conf. on Fusion Reactor Materials, Nov. 17-22, 1991, Clearwater, FL.

B. A. Loomis, L. J. Nowicki, and D. L. Smith (FPP), Tensile Properties of Vanadium and Vanadium-Base Alloys, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1991, Report No. DOE/ER/0313/10; published by ORNL.

B. A. Loomis, A. B. Hull, and D. L. Smith (FPP), Evaluation of Vanadium Alloys for Structural Material in a Fusion Reactor, presented at and to be published in Proc. of 5th Intl. Conf. on Fusion Reactor Materials, Nov. 17-22, 1991, Clearwater, FL.

B. A. Loomis and D. L. Smith (Fusion Power Program), Swelling Dependence of Neutron-Irradiated Vanadium Alloys on Temperature, Neutron Fluence, and Thermochemical Treatment, presented at 9th Topical Mtg. on Technology of Fusion Energy, Oak Brook, IL, Oct. 7-11, 1990.

P. S. Maiya and T. F. Kassner, Role of Atmospheric Corrosion of Aluminum Alloys in Viability of Intrinsic-Surface Methods for Tagging Military Hardware, ANL/ACTV-91/6 (1991).

P. S. Maiya, W. K. Soppet, J. Y. Park, T. F. Kassner, W. J. Shack, and D. R. Diercks, Stress Corrosion Cracking of Waste Container Materials, ANL-90/50 (1990).

K. Natesan and J. H. Park, Oxidation/Sulfidation Behavior of Fe-Cr Alloys: A Reactive-Element Effect, INVITED PAPER presented at 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 12-14, 1992.

K. Natesan, Corrosion Resistance of Iron Aluminides, INVITED PAPER presented at 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 12-14, 1992.

K. Natesan, Coatings for Improved Corrosion Resistance, INVITED PAPER presented at 3rd Intl. Conf. on Advances in Coatings and Surface Engineering for Corrosion and Wear Resistance, Newcastle, UK, May 11-15, 1992.

K. Natesan and J. H. Park, Oxidation/Sulfidation Behavior of Fe-Cr Alloys: A Reactive-Element Effect, INVITED PAPER presented at 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 12-14, 1992.

K. Natesan, J. H. Park, D. L. Rink, and C. A. Thomas (PETC), Performance of MHD Insulating Materials in a Potassium Environment, ANL/MHD-91/1 (1991).

K. Natesan, Corrosion Resistance of Iron Aluminides, INVITED PAPER to be presented at 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 12-14, 1992.

K. Natesan, Metal Wastage in Fluidized Bed Combustion Systems, INVITED PAPER to be presented at ASM Materials Week, Chicago, Nov. 2-5, 1992.

K. Natesan, W. Podolski (CMT), D. Y. Wang (CMT), F. G. Teats (CMT), W. Gerritsen (Rockwell Intl.), A. Stewart (Rockwell), and K. Robinson (Rockwell), Materials Performance in the Atmospheric Fluidized-bed Cogeneration Air Heater Experiment, ANL-91/4 (1992).

K. Natesan and W. Podolski (CMT), Materials Performance in Fluidized-Bed Air Heaters, presented at NACE Annual Conf. and Corrosion Show, Nashville, TN, April 27-May 1, 1992, Paper No. 125, pp. 1-13.

K. Natesan, Applications of Coatings in Coal-Fired Energy Systems, INVITED PAPER to be presented at Intl. Conf. on Metallurgical Coatings and Thin Films, San Diego, April 6-10, 1992.

K. Natesan, Materials Performance in Advanced Fossil Technologies, J. Metals, Vol. 43, No. 11, Nov. 1991, pp. 61-67.

K. Natesan, Combined Effect of Sulfur and Chlorine on Corrosion of Materials in Combustion Environments, presented at Illinois Coal Development Board's 9th Annual Contractor Technical Mtg., July 30-Aug. 1, 1991, Urbana, IL.

K. Natesan and D. Y. Wang (National Chung-Hsing U., Taiwan), Development of Weldments for Sulfur-Containing Combustion Environments, 1st Intl. Conf. on Heat Resistant Mater., Lake Geneva, WI, Sept. 22-26, 1991, eds. K. Natesan and D. J. Tillack, ASM Intl., Materials Park, OH, pp. 395-408.

K. Natesan and W. F. Podolski (CMT), Materials for FBC Cogeneration Systems, 1st Intl. Conf. on Heat Resistant Mater., Lake Geneva, WI, Sept. 22-26, 1991, eds. K. Natesan and D. J. Tillack, ASM Intl., Materials Park, OH, pp. 549-558.

K. Natesan, Corrosion Performance of Oxide-Dispersion-Strengthened Fe-Cr-Ni-Al Alloys in Coal Conversion Atmospheres, 5th Annual Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1991.

K. Natesan and J. H. Park, Corrosion and Mechanical Properties of Alloys in FBC and Mixed-Gas Environments, Advanced Research and Technology Development Fossil Energy Materials Program: Semiannual Progress Report for Period Ending September 30, 1990, ORNL/FMP-90/2 (Dec. 1990), pp., 303-318.

J. H. Park and P. Kostic (Serbian Academy of Science & Arts), Sensor Effect in $\text{YBa}_2\text{Cu}_3\text{O}_y$, Submitted to Microelectronics L.

J. H. Park, M. R. Fox, and G. Dragel, Development of Electrical Insulator Coatings for Liquid-Metal Blanket Applications, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

J. H. Park and K. Natesan, Oxidation Behavior of Iron-Chromium Alloys at Elevated Temperatures: A Reactive-Element Effect, ANL/FE-92/1 (1992).

J. H. Park, Materials Science in Solar Cell Development, INVITED PAPER presented at 1992 Spring Workshop in Energy Resources Session, Seoul, Korea, May 25-31, 1992.

J. H. Park, Surface Modification of High-Temperature Alloys: A Protective and Adhesive Scale-Forming Process, presented at 182nd Electrochemical Soc. Mtg., Toronto, Oct. 11-16, 1992.

J. H. Park, M. R. Fox, and G. Dragel, Development of Electrical Insulator Coatings for Liquid-Metal Blanket Applications, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

J. H. Park, Surface Modification of High-Temperature Alloys: A Protective and Adhesive Scale-Forming Process, presented at 182nd Electrochemical Soc. Mtg., Toronto, Oct. 11-16, 1992.

J. H. Park, High-Temperature Oxidation of Silicon/Oxygen/Nitrogen-Coated Alloys, presented at 182nd Electrochemical Soc. Mtg., Toronto, Oct. 11-16, 1992.

J. H. Park and K. Natesan, Oxidation of Copper and Electronic Transport in Copper Oxides, Submitted to Oxidation of Metals.

J. H. Park, Thermodynamic Measurements and Electronic Transport in Metal Oxide Systems, INVITED PAPER presented at Symp. for IUPAC Mtg., Snowbird, UT, Aug. 16-21, 1992.

J. H. Park and K. Natesan, Electronic Transport Properties in Copper Oxides, ANL-91/27, UC-400 (1991).

J. H. Park, K. Natesan and D. L. Rink, Sulfur and Oxygen Transport Properties of Thermally-Grown Cr_2O_3 Films, INVITED PAPER to 16th High Temperature Chemistry, Gordon Research Conf., Meriden, NH, July 23-27, 1990, to be published in High Temperature Science.

J. H. Park and K. Natesan, Alloy Grain-Growth in High-Temperature Oxidation, submitted to Electrochemical Soc. 180th Mtg., Phoenix, Oct. 13-18, 1991.

J. Y. Park, W. E. Ruther, T. F. Kassner, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors, INVITED PAPER to be published in Proc. 8th Water Reactor Safety Information Mtg., Oct. 22-24, 1990, Rockville, MD.

J.-H. Park, K. Natesan, and D. L. Rink, Sulfur and Oxygen Transport Properties of Thermally Grown Cr_2O_3 Films, INVITED PAPER for High Temp. Sci. Vol. 30, 1991, The Humana Press, Inc., pp. 193-219.

J.-H. Park and K. Natesan, Transport Properties and Oxidation in Chromium and Fe-Cr Alloys Exposed to Oxygen at High Temperatures, Intl. Conf. on Heat Resistant Alloys at High-Temperatures, Sept. 22-26, 1991, Lake Geneva, WI., ASM Intl., Materials Park, OH, eds. K. Natesan and D. J. Tillack, pp. 219-223.

D. T. Peterson (Iowa State U.), A. B. Hull, and B. A. Loomis, Hydrogen Embrittlement of Niobium-Base Alloys for Application in the ITER Divertor, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12.

D. T. Peterson (Illinois State U.), A. B. Hull, and B. A. Loomis, Hydrogen Embrittlement Considerations in Niobium-Base Alloys for Applications in the ITER Divertor, presented at 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

W. E. Ruther, T. F. Kassner, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking of Austenitic Stainless Steels in Simulated NPR Water, ANL/NPR-91/7 (1992).

W. E. Ruther, W. J. Shack, H. M. Chung, T. F. Kassner, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report, Oct. 1989-March 1990, NUREG/CR-4667 Vol. 10, ANL-91/5 (1991).

W. J. Shack, T. F. Kassner, J. Y. Park, W. E. Ruther, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors, Semiannual Report April-Sept. 1988, NUREG/CR-4667, ANL-89/40, Vol. 7 (1989).

W. J. Shack, P. D. Hicks, W. E. Ruther, H. M. Chung, T. F. Kassner, W. K. Soppet, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report Oct. 1990-March 1991, NUREG/CR-4667, Vol. 12, ANL-91/24 (1991).

T. Shoji (Tohoku U., Japan), T. Tomobe (Tohoku U.), Y. Watanabe (Tohoku U.), and H. M. Chung, Diagnosis of Thermal Aging of Cast Austenitic Stainless Steels, submitted to Symp. on Microstructures and Mechanical Properties of Aging Materials, TMS-AIME Fall Mtg., Nov. 1-5, 1992, Chicago.

H. C. Tsai, Y. Y. Liu, D. Y. Wang (Natl. Chung Hsing U., Taiwan), and J. M. Kramer (RE), Behavior of Low-Burnup Metallic Fuels for the Integral Fast Reactor at Elevated Temperatures in Ex-Reactor Tests, submitted to Intl. Conf. on Fast Reactors and Related Fuel Cycles (FR'91), Oct. 28-Nov. 1, 1991, Kyoto, Japan.

H. C. Tsai, D. Y. Wang, F. E. Savoie, and A. G. Hins, Fuel/Cladding Compatibility in Low-Burnup U-26Pu-10Zr/HT9 Fuel at Elevated Temperatures, ANL-IFR-152 (1991).

Patents

N. J. Carson (RE), R. A. Noland (HEP), and W. E. Ruther, Method of Removing Cesium from Steam. U.S. Patent No. 478,329, awarded May 7, 1991.

J. H. Park, Fabrication of Microceramic Tube by High Temperature Oxidation of Metal Foil, Wire or Other Structures. Patent application submitted May 14, 1991.

i

Mechanics of Materials

Section Manager: D. R. Diercks

Principal Investigators: M. C. Billone, A. M. Hassanein, S. Majumdar,

J. Y. Park, J. Rest, H. R. Thresh,¹ T. C. Wiencek

Support Staff: P. E. Domagala, S. A. Zawadzki

Postdoctoral Appointee: A. Stojimirovic

Technicians: W. F. Burke, D. R. Schmitt, T. M. Galvin, C. F. Konicek, D. R. Perkins,

S. L. Phillips, G. J. Talaber, J. C. Tezak, J. A. Zic

Secretary: P. J. Peterson

Visiting Scientist: A. E. Dwight¹

Student: W. A. Moll

The programs carried out by the Mechanics of Materials Section may be divided into three broad areas: (a) mechanical testing and component examination and analysis in support of light water reactor (LWR) technology, (b) mathematical modeling and analysis of structures and systems in support of nuclear and nonnuclear energy development, and (c) fabrication and nuclear fuel reprocessing. Current work in the first area includes ongoing programs for the environmentally assisted cracking of LWR structural components, metallurgical examination and mechanical testing of material from the lower head of the Three Mile Island Unit 2 (TMI-2) nuclear reactor, and analyses of failed components from operating nuclear power plants, together with a recently completed program on the stress corrosion cracking (SCC) of candidate nuclear waste canister alloys. In the second area, nuclear fuel behavior is being modeled for both LWRs and the Integral Fast Reactor (IFR), as well as for the Advanced Neutron Source (ANS). Analytical research activities in support of fusion energy development include stress analysis and development of design criteria for the first wall of the International Thermonuclear Experimental Reactor (ITER), computer analysis of tritium breeding and transport in the ITER blanket, and analyses of plasma/first wall interactions in fusion reactors. In the fabrication area, research is being conducted on fuel development and fabrication for the ANS, and support work for the Reduced Enrichment Research and Test Reactor (RERTR) is continuing. An experimental program on fuel fabrication and reprocessing for the IFR was also completed recently.

LWR Mechanical Testing and Component Examination

Environmentally Assisted Cracking in LWRs

Studies on the environmentally assisted cracking of piping and pressure vessels in LWRs are being conducted under an ongoing program sponsored by the NRC. These studies are being carried out in both the Mechanics of Materials Section and the Corrosion Section. Those activities performed in the Mechanics of Materials Section include measurement of cyclic crack growth rates (CGRs) in ferritic pressure-vessel and piping steels in boiling

¹Special Term Appointee.

water reactor (BWR) and pressurized water reactor (PWR) environments, and analytical and experimental analysis of environmental effects on the ASME Boiler and Pressure Vessel Code Section III fatigue design rules for ferritic steels.

Plain carbon and low-alloy steels are used extensively as piping and pressure vessel materials in PWRs and BWRs. Although operating experience with ferritic steels is better than with weld-sensitized austenitic SS, instances of cracking of ferritic steel components that form the reactor pressure boundary have occurred in the United States and abroad. Previous investigations of several ferritic steels showed that dissolved oxygen in coolant water promotes SCC. There also appears to be a strong correlation between sulfur content and distribution of the steels and susceptibility to SCC. Over the past 15 years, the corrosion fatigue properties of low-alloy steels in LWR primary-system water chemistries have been studied extensively. However, much less information is available on SCC of these materials. Because it is clear that very high CGRs can occur in some materials under some combinations of loading and environment, the objective of the current work is to better define the circumstances that can produce SCC in these steels.

Crack growth tests are being performed to determine threshold levels of the stress intensity factor as a function of environmental, material, and loading-history variables. The parameters include dissolved-oxygen concentration; anion and cation impurities; heat-to-heat variations; and metallurgical variables, including inclusion content and cladding with austenitic stainless steel. Crack-growth-rate tests were performed on high- and low-sulfur A533-Gr B steel and A106-Gr B steel under a cyclic loading (sawtooth wave shape with 1-sec unloading time) at 0.08 Hz with a load ratio $R = 0.2$ in deionized water at 289°C. CGRs for the three alloys were bounded by the proposed ASME Section XI fatigue growth curves for low-alloy steels.

Tests are also being conducted on A533-Gr B pressure vessel steel specimens that are plated with nickel-chromium to simulate austenitic SS cladding on a reactor pressure vessel, and hence to determine the validity of using data obtained from specimens without cladding to analyze the behavior of a clad ferritic vessel where only the crack surface is exposed to the environment. The observed CGRs are higher than the predicted values at rise times of 25 to 1200 sec. The CGR at a rise time of ≈ 350 sec is greater by one order of magnitude than the predicted value. At rise times outside this range, the observed CGRs were bounded by the ASME correlation. The magnitude of the environmental enhancement predicted by the correlation is adequate to bound the data; it is the onset or threshold for the enhancement that is predicted nonconservatively. Most of the data on which the correlation for the threshold is based were obtained for rise times of ≈ 10 -60 sec, so extrapolation to longer rise times may be inaccurate or the apparent nonconservativeness may be an effect of the clad. Further testing is needed to resolve this issue.

Recent tests conducted by several investigators in the United States, Japan, and Germany have shown that fatigue lives of low-carbon steels in water containing ≥ 0.2 ppm oxygen can fall below the design fatigue curve given in Section III of the ASME Boiler and Pressure Vessel Code. The safety factors built into the ASME Code curve were intended to guard against uncertainties related to material surface roughness, heat-to-heat variation, etc., but were not intended to account for effects of stress corrosion fatigue. Therefore, these recent results have raised concern at the NRC about application of the ASME Code to

these recent results have raised concern at the NRC about application of the ASME Code to existing BWRs in the United States. When extrapolated to strain rates typically experienced by the BWR components, they predict losses of life by factors of ≥ 1000 compared to those in air, thus wiping out all safety margins included in the ASME Code design curve.

Most of the fatigue tests in a water environment, however, were conducted at strain ranges that are greater than those expected in a BWR. Pending generation of data at reactor-relevant strain ranges, the NRC has requested that ANL develop interim design-fatigue curves for low-carbon steel, low-alloy ferritic steel, and stainless steel to account for the environmental effects of oxygen-containing water. Development of these curves is based on available data and engineering judgement. We are currently estimating the fatigue lives in reactor-relevant environments and strain ranges on the basis of crack growth and material behavior models. Initial results suggest that the loss in life with decreasing strain rate should saturate at a strain rate of $\approx 10^{-5}$ /sec. Thus, the life-reduction factors of ≥ 1000 predicted by the empirical fit to the data are unduly conservative.

TMI-2 Vessel Integrity Program

Studies are being conducted to determine the extent of the damage suffered by the TMI-2 nuclear reactor as a result of the 1979 loss-of-coolant accident. The lower head of the reactor pressure vessel did not fail, even though approximately 20 metric tons of molten core debris fell onto it during the accident. The objectives of the present program are to determine a scenario for, and deduce the temperatures of, the steel in the lower vessel head during the accident; determine the mechanical properties of the steel from the lower head under the accident conditions; and assess the integrity of the TMI-2 vessel during the accident. This program is sponsored by the NRC and the Organisation for Economic Co-operation and Development (OECD), and the research is being conducted by ANL, the Idaho National Engineering Laboratory (INEL), and participating member countries of the OECD.

Fifteen samples recovered from the TMI-2 lower head and sent to ANL have been examined in detail by optical metallography and scanning electron microscope analysis. These examinations, in conjunction with follow-on work conducted by INEL, have determined that a roughly circular "hot spot" approximately 0.9 m in diameter developed in one quadrant of the lower head during the accident, and that the maximum temperature at the center of the hot spot approached 1100°C. Creep and tensile tests at 600 to 1200°C are presently being completed on test specimens taken from the lower head samples. These mechanical property data will be used in the stress and thermal analysis of the lower head to be conducted by INEL to determine the lower head's margin-to-failure.

Materials for Advanced-Reactor Safety Systems

A number of advanced nuclear reactor power plant concepts are under development in the United States, including advanced LWRs and—in the longer term—advanced HTGRs and metal-cooled reactors. These concepts generally feature simplified modular design and construction, passive safety systems, and projected improvements in reliability and

contrast to the typical 40-yr design lives of the current generation of LWRs. It is anticipated that approximately four midsize (≈ 600 MWe) advanced-concept water-cooled reactor designs will be submitted to the NRC for design certification by 1996, with gas- and sodium-cooled designs to follow. The objectives of this newly initiated program are to (a) evaluate these proposed advanced reactor designs and the materials of construction for the safety systems, (b) identify all aging-related degradation mechanisms for materials of construction, and (c) evaluate from the safety viewpoint the suitability of the proposed materials for the design application.

Analysis of Failed Components from Nuclear Power Plants

This activity, which has been carried in the Mechanics of Materials Section for several years, is sponsored primarily by Commonwealth Edison Company, although analyses are occasionally performed for other electrical utilities. The objectives of the analyses are typically to determine the root cause(s) of failure and to suggest remedial action to avoid similar failures. Analyses commonly include the use of nondestructive, metallographic, and SEM examinations, as well as chemical and X-ray diffraction analyses of radioactively contaminated samples.

Mathematical Modeling and Analysis

Fuel Behavior in the Integral Fast Reactor

The LIFE-METAL computer code has been developed as an extension of the LIFE code to analyze the thermal and mechanical performance of metallic fuel elements under IFR operating conditions. Significant progress has been made recently in validating LIFE-METAL for use in qualifying the new driver fuel for the EBR-II reactor. The fuel composition U-20Pu-10Zr with either ferritic HT9 (Mark-V design) or austenitic 316 SS (Mark-VA design) cladding has been chosen for the new driver fuel. In particular, LIFE-METAL is used to predict the thermal, mechanical, and lifetime performance of this fuel under normal operation conditions. In addition to extensive validation of the models for predicting performance parameters (e.g., fission gas release/retention, fuel axial strain, and cladding diametral strain profile) that are routinely measured for experimental fuel elements, fuel/cladding mechanical interaction (FCMI) and fuel/cladding metallurgical or chemical interaction (FCCI) have been modeled more accurately and have been shown to affect the design life of the new fuel. Based on LIFE-METAL design analyses with these models, the Mark-V and -VA design operating conditions are being modified to ensure a lifetime of 10 at.% burnup with a large design margin ($< 1/3000$ predicted fuel pin failures). At the same time, because of the significant impact of these calculations on the design, additional data have been requested and prioritized to validate the extrapolation of the FCMI and FCCI models to design temperatures (with 3σ uncertainties) higher than those of the existing experimental fuel elements.

VICTORIA Code Development

Argonne has played a major role in developing and implementing the VICTORIA computer code, which calculates fission-product release and transport under accident conditions in LWR rubble-bed and molten-pool-degraded fuel morphologies. Modeling of these processes is an essential aspect of severe-reactor-accident analysis. Fission-product transport through the rubble bed is based on single-phase flow through a permeable medium with sources provided by species released from the bed debris. Fission-product transport through the molten pool is based on models for atomic diffusion in a liquid, volume diffusion of bubbles, bubble rise under the forces of buoyancy, and bubble interaction and coalescence. Once fission product transport to the top of the liquid pool has been calculated, subsequent release to the bulk gas above the pool occurs through a partial-pressure driving force according to Raoult's law. ANL is currently performing VICTORIA code validation against data from both in-reactor and out-of-reactor experiments.

Advanced Neutron Source

Development of the design for the Advanced Neutron Source (ANS), a new high-flux research and test reactor, is underway at Oak Ridge National Laboratory. This reactor concept will require nuclear fuel to operate satisfactorily at temperatures and neutron flux levels never before encountered. The Section is modeling the behavior of fuels proposed for this reactor. A leading candidate is U_3Si_2 dispersed in a suitable matrix material. Recent modeling activities have focused primarily on two irradiation-induced phenomena in U_3Si_2 , i.e., grain recrystallization and the crystalline/amorphous transition.

Grain recrystallization has been identified as a potential explanation for the observed "knee" in the U_3Si_2 swelling curve for low-temperature ($\approx 200^\circ\text{C}$) irradiations. This phenomenon has been observed in high-burnup UO_2 , and preliminary observations on irradiated U_3Si_2 fuel plate indicate that it may also occur at higher temperatures ($\approx 450^\circ\text{C}$) and fission rates. A theoretical formulation of this phenomenon has been developed in which the stored energy in the material is concentrated in a network of recrystallization sites (e.g., triple points of subgrain boundaries and cellular dislocation structure) that diminish with dose due to interaction with radiation-produced defects (vacancy-impurity pairs). Recrystallization is induced when the energy per site is high enough that the creation of grain-boundary surfaces is offset by the creation of strain-free volumes, with a resultant net decrease in the free energy of the material. The resulting mathematical formulation provided a reasonable description of the behaviors of UO_2 and U_3Si_2 at lower temperatures. However, for U_3Si_2 at higher temperatures and fission rates, it failed to adequately describe the observed swelling. A more general and less restrictive physical model was therefore developed, and initial assessments of the resulting mathematical formulation indicate that it can describe the behavior of U_3Si_2 at higher temperatures and fission rates.

The transformation of U_3Si_2 from the crystalline to the amorphous state under ion radiation has recently been observed, and evidence exists that the same phenomenon may occur under neutron irradiation. For this reason, a phenomenological description of the potential transformation has been developed on the basis of a synthesized thermodynamic

treatment of nucleation theory and a rate-theory formulation of the growth of irradiation-induced amorphous clusters. The model reproduces the trends of the U_3Si_2 ion irradiation data.

ITER Stress Analysis and Design Criteria

The blanket of the ITER, particularly its first wall, will be subjected to high cyclic stresses from surface heat flux and plasma-disruption-induced electromagnetic loading. In addition, the blanket will be subjected to a steady internal pressure of 1 atm. The surface heat flux alone will likely be high enough to cause the maximum stress to exceed the $3S_m$ limit of the structural material (annealed Type 316 stainless steel). As a result, the material will undergo cyclic plastic strain. There are two concerns for such high cyclic thermal stress: (a) ratcheting (i.e., accumulation of plastic strain with cycles), and (b) fatigue.

The elastic-ratcheting rules of the ASME Code were derived for cylindrical geometry under internal pressure. They are not applicable to ITER because the first wall of the ITER is a plate subjected to bending stresses. Therefore, detailed elastic-plastic finite-element analyses (the first such analysis for a fusion reactor in the United States) of a complete ITER blanket module have been initiated to analyze ratcheting with imposed thermal cycles. Initial results suggest that shakedown will occur rapidly up to a surface heat flux of $\approx 0.4 \text{ MW/m}^2$. Above this flux level, the maximum plastic strain increases at a diminishing rate with cycle. To date, the analysis has been conducted for four cycles at a surface heat flux of 0.6 MW/m^2 without shakedown. More cycles must be analyzed before any conclusion can be drawn about ratcheting. Future analyses will also include the effects of cyclic disruption-induced pressure loading on ratcheting.

Analysis of Plasma/First Wall Interactions

Modeling and analyses are being performed on the effects of high thermal loadings from the plasma on both the divertor plate/wall coating and on the substrate structure. This problem continues to be a major issue with respect to the feasibility and successful operation of a magnetically confined fusion reactor.

The intense deposition of energy on plasma-facing components during a plasma disruption may cause severe surface erosion, and the exact amount of material eroded is very important to reactor design and reactor lifetime. The wall material ablated during a disruption can interact with the incoming plasma particles, and the resulting shielding effect may prolong component lifetime and increase the reactor duty cycle. The impact of the vapor shielding effect is being evaluated with a comprehensive dynamic model that describes the various interaction processes between the plasma particles (both ions and electrons) and the expanding eroded wall material. The generated photon radiation spectra and their transport through the vapor to the wall are also modeled. The model shows good agreement with experimental data on disruption.

Heat flux on the divertor plate of a fusion reactor is probably the major limiting constraint on its lifetime. The current heat flux profile on the outer divertor plate of a device like the ITER has a narrow and highly peaked profile. The peak heat flux can be as

high as 30-40 MW/m², with full width at half maximum of a few centimeters. Sweeping the heat load along the divertor plate has been proposed to reduce the thermomechanical effects of this highly peaked narrow profile. The effectiveness of the sweeping process is being modeled and investigated parametrically for various design values. The optimum sweeping parameters of a particular heat load will depend on the design of the divertor plate, as well as on the profile of such a heat load. In general, moving a highly peaked heat load results in substantial reduction of the thermomechanical effects on the divertor plate.

Tritium Breeding and Transport

This activity consists of modeling tritium and helium transport/retention in fusion reactor blanket materials, coordinating experimental efforts to better determine model parameters and validate computer codes, and performing design calculations. During the past year, effort was concentrated on the models and data base for tritium-breeding Li₂O and neutron-multiplying Be, because of the selection of these materials as prime candidates for the ITER breeding blanket. The tritium retention/release models (e.g., diffusion, desorption, adsorption, and solubility) have been incorporated into the steady-state and transient DISPL2 transport code, which is currently being validated to the transient release data from the in-reactor purge-flow BEATRIX-II experiment conducted in the Fast Flux Test Facility. While good agreement with data has not been achieved to date, a significant contribution was made to the program by highlighting certain system and instrumentation effects that tend to distort the time response of the experimental release signal. An analytical and experimental plan has been adopted to improve data interpretation and resolve discrepancies between predictions and data.

Models and design correlations have been developed and adopted by the ITER design community to calculate tritium retention in Be- and He-induced swelling. Close collaboration (test planning and data analysis) has been maintained with Pacific Northwest Laboratories (PNL), where the Be experimental work is being conducted for ITER. Again, our main contribution to this effort this year has been in proposing models, determining the limitations of the data base, and planning additional measurements and new experiments to improve our predictive capability in this area.

Concurrently with the modeling, planning of experiments, data analysis, and code validation, we perform design calculations on a routine basis. The ranges of design operating conditions help to narrow the scope of the modeling and the experimental work to some extent.

Intense Pulsed Neutron Source

In a special three-month project assigned to the Mechanics of Materials Section, we participated in the Laboratory Director's Special Task Force on IPNS Operation with Leaking Booster Target. The fission-product monitor of IPNS had detected larger-than-allowed traces of radioactive xenon, which indicated that at least one of the Zircaloy-clad uranium disks was leaking fission products into the water coolant. The basic issue was whether to shut down IPNS and replace the whole target or to request an increase in

allowable xenon release. Modeling of the chemical interaction of water/steam and uranium and the consequences of both oxidizing and hydriding of the uranium indicated that the system should not be operated with any indication of uranium/water contact and interaction. Because of oxidizing and hydriding of the cladding, even a small pinhole leak would eventually grow to the point where disk swelling and fission product release would become a serious problem. Based largely on this analysis, the Laboratory decided to replace the IPNS target. Members of the Mechanics of Materials Section are now participating in a design group to redesign the target.

Fabrication and Nuclear Fuel Reprocessing

Integral Fast Reactor

As part of the IFR program, a Fuel Cycle Demonstration is focused on processing spent irradiated fuel elements to recover U and Pu for future fuel inventory. Fissile material recovery by electrorefining yields a porous cathode product contaminated with Cd and an LiCl/KCl mixture or a liquid cathode product as a solid ingot of Cd containing fissile metal and a compound of the type UCD_{11} . A cathode processor is planned for removal of the contaminants and consolidation of the fissile material. A Cathode Processor Simulation Experiment (CPSE) has been carried out to support the reference design activity and to demonstrate process viability for the solid cathode product.

The viability of refining liquid cathode ingots has been examined in the CPSE investigations. A maximum charge of 2,908 g of liquid cathode was processed to yield a 292 g ingot of uranium. The large (≈ 90 wt.%) Cd condensate transfer associated with this type of charge is handled consistently, and the impurity levels in the ingot compare well with those in the refined solid cathode.

Numerous container materials for the process have been evaluated, beginning with graphite coated with ZrO_2 , Al_2O_3/MgO , and Y_2O_3 . While all of these coatings provided satisfactory carbon control in the melt, none survived for more than one melt. A majority of the process development trials used a recrystallized Al_2O_3 crucible, which provided satisfactory results but is easily fractured in a remote-handling environment. ZrO_2/Y_2O_3 performed similarly, but has the same deficiency. TiC and TiCN crucibles were found to be wetted by the refined metal. The most promising crucible material appears to be Tribacor 532N, a nitrided Nb-30% Ti-20% W alloy by weight. This crucible material was used for one uranium and two solid cathode material trials and produced good-quality ingots that released readily from the crucible. Its good ductility also makes the material a candidate for remote-handling applications.

Reduced-Enrichment Research and Test Reactor

The RERTR program supports the nuclear nonproliferation policies of the federal government. A keystone of this program is the development and utilization of low-enrichment, high-density, uranium-bearing fuels for use as dispersed-phase powders in plate-type elements. The irradiation performance of U_3Si_2 has been found to be very good

up to high fuel burnup, and, through ANL technology transfer, this fuel is now commercially available for core conversions. At a typical enrichment of $19.7 \pm 0.2\%$, diversion of this fuel alloy from fabrication facilities or reactors to weapons use, either before or after irradiation, is precluded.

The Section is now focusing its activities on (a) development of techniques to improved fuel loading homogeneity through better characterization of the initial powders and improved fabrication methods; (b) development of improved analytical techniques, including digital X-radiography, for the characterization of fabricated fuel plates; and (c) continuation of technology transfer with domestic and foreign fabricators to enhance their knowledge of U_3Si_2 and their ability to fabricate plate-type elements with this fuel.

Advanced Neutron Source Reactor

In addition to the fuel modeling work for the ANS described above, the Section is also involved in development and fabrication of fuels for this reactor concept. A total of 18 "fuel holders" have been fabricated and irradiated in the Oak Ridge High Flux Isotope Reactor, and a second set of 18 fuel holders has been produced. Additional sets of holders with improved porosity uniformity are planned for fabrication during the current fiscal year. Fuels incorporated into the test matrix include U_3Si , U_3Si_2 , UAl_x , UAl_2 , and U_3O_8 .

In concert with Babcock & Wilcox (Lynchburg, VA), fabrication and inspection techniques are being examined and tested to produce fuel plates with controlled fuel gradients across both the width and the length of a fuel plate. Fundamental studies of fuel powder characteristics and their relationship to uniformity of the fuel plate loading are currently underway. Preliminary results have been applied to current fabrication methods and have resulted in increased uniformity of test fuel plates. Effort continues on digitizing the output of the B&W X-ray attenuation fuel plate scanner. In addition, methods are being investigated for digitizing the standard X-ray films and for performing digital image processing and analysis on these films.

Fabrication of Actinide Burnup Dosimeters

The primary objective of this activity is to design and fabricate dosimeter capsules for EBR-II experiments to determine the fission and neutron capture rates in four minor actinides. These nuclides, Np^{237} , Pu^{240} , Am^{241} , and Am^{243} , are responsible for the long-term radiological hazards of spent nuclear fuel. The EBR-II experiments will demonstrate that an IFR-type fast reactor can fission these nuclides at a rate sufficient to convert the radiological hazard of the nuclear waste to a short-term problem.

Dosimeters are being fabricated for a ten-day run and three one-year runs at full power. Three nuclides, U^{328} , U^{235} , and Pu^{239} , will be inserted along with the four actinides as controls to compare their fission cross sections and yields with published data. Dosimeters with Co, Cu, Fe, Ni, and Ti will also be included to further characterize the EBR-II neutronics during the experiment.

A total of 174 vanadium metal dosimeters, with loadings of 7 to 9 mg of one of the above materials, will be fabricated. Two dosimeter types will be made: (a) 1.27-mm-diameter capsules 8.64 mm in length for specimens in wire form, and (b) 2.79-mm-diameter capsules 3.05 mm in length for foils or powder. Both types will be gas-tungsten-arc seal welded and inspected to meet the quality assurance requirements for EBR-II experiments. Glovebox fabrication facilities now being prepared will include a remote television monitoring system for handling the minute capsules, and shielding for working with the Pu^{240} , Am^{241} , and Am^{243} nuclides. Trial welds of both capsule types have been made and characterized, resulting in modifications to the vanadium capsules. In addition, the required experimental nuclides are being procured and the required documentation of fabrication and inspection procedures is being prepared.

Removal of Lead from Copper-Based Alloys

An experimental program is being conducted in conjunction with the Energy Systems Division to develop a practical method for removing or substantially reducing lead levels in commercial copper-based alloys and scrap. This work is being conducted under a Cooperative Research and Development Agreement (CRADA) between ANL and the Brass and Bronze Environmental Research Corporation. Several slagging systems that use relatively inexpensive mineral additions are being explored for the selective removal of lead.

Recent Work by the Mechanics of Materials Section

Publications

O. K. Chopra and W. J. Shack, Evaluation of Aging Degradation of Structural Components, INVITED PAPER presented at NRC Aging Research Information Conf., March 24-27, 1992, Rockville, MD.

O. K. Chopra, W. J. Shack, and S. T. Rosinski (Sandia National Laboratories), Radiation Embrittlement of the Neutron Shield Tank from the Shippingport Reactor, NUREG/CR-5748, ANL-91/23, SAND91-1933 (1991).

O. K. Chopra, H. M. Chung, and W. J. Shack, Materials Studies on Service-Aged Components, To be published in Compilation of Contract Research for the Materials Engineering Branch, Div. of Engineering: Annual Report. for FY 1990 by Office of Nuclear Regulatory Research, U.S. Nuclear Regulatory Commission.

H. M. Chung, T. F. Kassner, J. Y. Park, W. E. Ruther, J. E. Sanecki, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors (condensed version), to be published in Compilation of Contract Research for the Materials Engineering Branch Division of U.S. Nuclear Regulatory Commission Engineering Annual Report for FY 1990, NUREG-0975, Vol. 8.

H. M. Chung, T. F. Kassner, W. J. Shack, W. E. Ruther, J. Y. Park, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-Sept. 1990, NUREG/CR-4667 Vol. 11, ANL-91/9 (1991).

D. R. Diercks and L. A. Nelmark, TMI-2 Vessel Investigation Project (VIP) Metallurgical Program, to be published in Compilation of Contract Research for the Materials Engineering Branch Division of U.S. Nuclear Regulatory Commission Engineering Annual Report - Jan. 1991.

P. E. Domagala, J. Rest, and S. A. Zawadzki, Assessment of Improved Fission-Product Transport Models in VICTORIA Against the ORNL HI VI Tests, INVITED PAPER for 27th ASTM/AICHE/ANS Natl. Heat Transfer Conf., Minneapolis, July 28-31, 1991, pp. 182-189.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, presented at NRC Aging Res. Info. Conf., March 24-27, 1992, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, W. K. Soppet, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-September 1991, NUREG/CR-4667, Vol. 13, ANL-92/6 (1992).

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, INVITED PAPER presented at 19th Water Reactor Safety Information Mtg., Rockville, MD, Oct. 28-30, 1991.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, W. K. Soppet, and W. J. Shack, *Environmentally Assisted Cracking in Light Water Reactors Semiannual Report April 1991-September 1991*, NUREG/CR-4667, Vol. 13, March 1992.

T. F. Kassner, J. Y. Park, W. E. Ruther, W. J. Shack, D. R. Diercks, and W. K. Soppet, *Environmentally Assisted Cracking in Light Water Reactors, Semiannual Report*. Oct. 1988-March 1989, NUREG/CR-4667, ANL-90/4, Vol. 8 (1990).

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, *Fatigue and Environmentally Assisted Cracking in Light Water Reactors*, presented at 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, *Fatigue and Environmentally Assisted Cracking in Light Water Reactors*, Proc. 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Bethesda, MD, NUREG/CP-0119, Vol. 1, pp. 127-150.

T. F. Kassner, J. Y. Park, W. E. Ruther, W. J. Shack, and W. K. Soppet, *Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-Sept. 1989*, NUREG/CR-4667 Vol. 9, ANL-90/48 (1991).

D. S. Kupperman, S. Majumdar, J. S. Gregar (CD), J. P. Singh, S. Dorris, N. Gopalsami, S. Dieckman, A. C. Raptis, R. A. Valentin, and T. K. Hunt (ERIM), *Materials Research for Sodium Engine Development*, to be published in Proc. 26th Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

D. S. Kupperman, S. Majumdar, J. P. Singh, and A. Saigal, *The Application of Neutron Diffraction Time-of-Flight Measurements to the Study of Strain in Composites*, INVITED PAPER presented at NATO Advanced Research Workshop on "Measurement of Residual Stress & Applied Stress Using Neutron Diffraction," Oxford, UK, March 18-22, 1991.

D. S. Kupperman, S. Majumdar, and J. P. Singh, *Application of Neutron Diffraction to the Determination of Residual Strain in Advanced Composites*, INVITED PAPER submitted to J. Neutron News.

D. S. Kupperman, J. P. Singh, and S. Majumdar, *Use of Neutron Diffraction in the Measurement of Residual Strains in Composites*, presented at Ann. Spring Mtg. of Am. Ceram. Soc., Cincinnati, April 1991.

B. A. Loomis, C. F. Konicek, L. J. Nowicki, and D. L. Smith (FPP), *Tensile Properties of Vanadium-Base Alloys with a Tungsten-Inert-Gas Weld Zone, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending March 31, 1992 - Report No. DOE/ER-0313/12*.

P. S. Malya, W. K. Soppet, J. Y. Park, T. F. Kassner, W. J. Shack, and D. R. Diercks, *Stress Corrosion Cracking of Waste Container Materials*, ANL-90/50 (1990).

S. Majumdar, Ratcheting Problems for ITER, J. of Fusion Tech., Vol 21, Jan. 1992.

S. Majumdar, J. P. Singh, D. S. Kupperman, and A. D. Krawitz (U. of Missouri, Columbia), Application of Neutron Diffraction to Measure Residual Strains in Various Engineering Composite Materials, J. of Eng. Mater. and Tech., Jan. 1991, Vol. 113, pp. 51-59.

L. Millard (Utah State U.) and J. Rest, LIFE-METAL Computer Code Validation Testing, Summer 1991 Student Research Participation Program Report.

J. Y. Park, W. J. Shack, and D. R. Diercks, Crack Growth Behavior of Candidate Waste Container Materials in Simulated Underground Water, for presentation at Symp. on Application of Accelerated Corrosion Tests to Service Life Prediction of Materials, Miami, Nov. 16-17, 1992.

J. Y. Park, W. J. Shack, and D. R. Diercks, Crack-Growth-Rate Testing of Candidate Waste Container Materials, to be published in Proc. of FOCUS '91, Las Vegas, Sept. 29-Oct. 2, 1992.

J. Y. Park, W. E. Ruther, T. F. Kassner, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors, INVITED PAPER to be published in Proc. 8th Water Reactor Safety Information Mtg., Oct. 22-24, 1990, Rockville, MD.

J. Rest, Fission Gas Bubble Nucleated Cavitation Void Swelling of the Alpha-Uranium Phase of Irradiated U-Pu-Zr Fuel, presented at Effects of Radiation on Materials: 16th Intl. Symp., June 21-22, 1992, Denver.

J. Rest, A Phenomenological Model for a Radiation-Induced Crystalline to Amorphous Transformation in U_3Si_2 , Submitted to Evolution of Microstructure in Metals During Irradiation, Minett, Muskoka, Canada, Sept. 29-Oct. 3, 1991.

J. Rest and G. L. Hofman, A Mechanistic Description of Swelling of U-Pu-Zr Fuel, To be presented at 16th Symp. on Effects of Radiation on Materials, June 21-22, 1992, Denver.

W. E. Ruther, T. F. Kassner, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking of Austenitic Stainless Steels in Simulated NPR Water, ANL/NPR-91/7 (1992).

W. E. Ruther, W. J. Shack, H. M. Chung, T. F. Kassner, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report, Oct. 1989-March 1990, NUREG/CR-4667 Vol. 10, ANL-91/5 (1991).

A. Saigal (Tufts U.) and S. Majumdar, Analysis of Monolithic Solid Oxide Fuel Cells, presented at and for publication in Proc. of 1992 ANSYS Technology Conf., Pittsburgh, May 4-7, 1992.

A. Saigal, D. S. Kupperman, and S. Majumdar, Residual Strains in Titanium Matrix, High Temperature Composites, J. Mater. Sci. & Eng., A150 (1992), pp. 59-66.

W. J. Shack, P. D. Hicks, W. E. Ruther, H. M. Chung, T. F. Kassner, W. K. Soppet, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report. Oct. 1990-March 1991, NUREG/CR-4667, Vol. 12, ANL-91/24 (1991).

J. P. Singh, D. S. Kupperman, S. Majumdar, S. E. Dorris, N. Gopalsami, S. L. Dieckman, R. A. Jaross, D. L. Johnson, J. S. Gregar, R. B. Poeppel, A. C. Raptis, and R. A. Valentin, Sodium Heat Engine Development Program: Phase I Final Report, ANL-91/45 (1992).

J. P. Singh, D. S. Kupperman, and S. Majumdar, Strengthening of Composites by Internal Stresses: Determination by Neutron Diffraction, INVITED PAPER presented at 1st Intl. Symp. on the Science of Engineering Ceramics, Koda, Japan, Oct. 21-23, 1991.

J. P. Singh, S. Majumdar, A. S. Wagh, T. Wenzel, and R. B. Poeppel, Materials Qualification Technology for Ceramic Cross-Flow Filters, ANL/FE-91/1 (1991).

J. P. Singh, D. S. Kupperman, and S. Majumdar, Role of Internal Stresses in Improvement of Mechanical Properties of Ceramic Composites, INVITED PAPER presented at 44th Pacific Coast Regional Mtg. of the Amer. Ceram. Soc., San Diego, Oct. 31-Nov. 2, 1991.

A. Stojimirovic and S. Majumdar, Use of the PRAISE Code to Estimate Probability of Leaks in the NPR-HWR Pressurizer Surge Line, ANL/NPR-92/4 (1992).

T. C. Wiencek, H. R. Thresh and J. R. Summers, Development of a Boron-Copper Neutron Absorber Composite, ANL-91/44 (1991).

Tribology

Section Manager: F. A. Nichols

Principal Investigators: R. A. Erck, A. Erdemir, G. R. Fenske

Support Staff: D. E. Busch

Technician: R. H. Lee

Secretary: D. K. Moores

Postdoctoral Appointee: O. O. Ajayi

Visiting Scholar: X. Pan (People's Republic of China)

Students: J. Ockers,¹ J. Pagan,² J. Prunoske,³ D. Schult¹

The Tribology Section conducts research and development on low-friction and wear-resistant surface coatings and treatments applied to ceramic and high-temperature metal substrates, for use under high load at high temperatures in aggressive chemical atmospheres. These coatings are primarily intended to protect engine-component surfaces undergoing sliding and rolling contact in low-heat-rejection diesels, automotive gas turbines, and other advanced engines being developed under the sponsorship of the DOE Office of Transportation Technologies, and U.S. industry. In addition, the Section provides technical direction and administrative support to the DOE Office of Transportation Materials within the Office of Transportation Technologies.

Engineered Tribological Interfaces

This project explores the factors that control the tribological properties of surfaces and is attempting to develop high-temperature, low-friction, wear-resistant surfaces by the application of coatings and/or the use of surface-modifying treatments such as ion implantation. Program emphasis is on developing low-friction, wear-resistant coatings on ceramic and other materials intended for utilization in components for low-heat-rejection diesels and other high-temperature advanced engines and engine power trains. Our research is in three major areas: (a) development of low-friction and low-wear surfaces by a variety of surface-modification methods, including physical-vapor-deposition techniques (ion-beam-assisted-deposition, plasma sputtering, and thermal evaporation); (b) development of ultrahard, low-friction diamond, diamondlike, and other similar coatings by plasma-assisted chemical vapor deposition; and (c) tribological testing and characterization of surfaces before and after modification and coating.

Coating by Physical Vapor Deposition

A major effort in the Tribology Section has focused on the design and construction of a sophisticated and versatile facility for the ion-beam-assisted deposition of low-friction, low-

¹University of Illinois at Urbana-Champaign.

²University of Michigan.

³Alfred University.

wear coatings. This facility consists of a large, ultrahigh-vacuum chamber with two individually controlled electron-beam evaporation sources and simultaneous or sequential ion sources that produce ions with energies from a few eV up to 1500 eV. A six-degree-of-freedom specimen manipulator, including rotational motion, ensures uniformity in the coating of complexly shaped substrates and can support and manipulate complex engine components such as piston rings and liners. In addition, the Section has a large commercial sputtering apparatus for the deposition of lubricious coatings and recently has developed an ultrahigh-vacuum apparatus for depositing fullerene compounds as tribological coatings.

Accomplishments to date include:

- Development of silver coatings on alumina, zirconia, and silicon nitride ceramic substrates, which reduced the wear rates by factors of 10 to 3500, depending on load, temperature, velocity, and substrate. Friction was also reduced by one-half to one-third, depending on temperature, at temperatures up to 400°C. Recent tests with synthetic liquid lubricants show a synergistic effect on both wear and friction, with improvements in both properties when a liquid lubricant is used in conjunction with a silver-coated ceramic.
- Deposition of boron oxide coatings on superalloys and ceramics, which virtually eliminate all measurable wear and provide extremely low (<0.05) coefficients of friction over a wide range of loads and at temperatures up to 200°C. The mechanism responsible for these coatings is the formation of boric acid in the presence of atmospheric moisture. Boric acid is a layered-structure material with a very low resistance to interlayer shear; it is quite analogous to the solid lubricant molybdenum disulfide. Efforts are underway to transfer this technology to industry via licensing agreements and CRADAs.
- Deposition of dense metallic seal-coatings on porous ceramic that serve as thick thermal barrier coatings (TTBCs) in advanced diesel engines. Such coatings are necessary to eliminate absorption of fuel by TTBCs, which degrade engine efficiency. With IBAD processing, we found that a thin, dense metallic coating (Ag or an Nb/Cr alloy) could be deposited on porous zirconia TTBCs, with the coating filling in or covering large open pores that intersect the surface.
- Evaluation of tribological properties of bearing steels coated with fullerene compounds. Preliminary results indicate the friction and wear of uncoated steel balls slid against fullerene-coated steel discs are reduced depending on the applied load. Higher loads resulted in lower friction and improved wear performance relative to uncoated substrates.

Plasma-Assisted Chemical Vapor Deposition of Diamond and Diamondlike Coatings

The Tribology Section's recently installed microwave plasma deposition source allows the production of diamond and diamondlike-carbon and similar ultrahard coatings on ceramics and other high-temperature materials. Efforts are underway to characterize the effects of deposition processing conditions on the properties of polycrystalline diamond (PCD) films deposited on pure elements (e.g., Si, Nb, and Be) and advanced ceramics (e.g. SiC and Si₃N₄); see the SEM image below. The main thrust of the PCD effort is to produce smooth, adherent diamond films that can be used as lubricious, wear-resistant coatings without causing severe wear of mating components.

The Section has also been active in evaluating diamondlike-carbon coatings produced for us by Colorado State University, which is currently developing a wide-angle, high-density, high-flux metal-ion source under subcontract to ANL. Preliminary evaluation of these coatings has been very promising: limited measurements indicate extremely low wear rates and friction coefficients.

Tribological Testing and Surface Characterization

In support of our coating and surface-modification research, we have developed extensive state-of-the-art facilities for tribological evaluation and surface characterization. Our current tribological equipment includes high-temperature (up to 900°C) reciprocating pin-on-flat and rotational pin-on-disc friction and wear test machines; a low-temperature, controlled-environment pin-on-disc machine; a high-resolution surface profilometer; a high-temperature (600°C) pin-on-disc test machine installed in an environmentally con-

SEM image of cross section of a 45-μm-thick polycrystalline diamond film deposited on a silicon substrate with microwave-plasma deposition system

Photograph of high-temperature pin-on-disc apparatus used to evaluate tribological properties of fullerene compounds under controlled environments

trolled glovebox (see photo above), and an adhesion-force tester. Computerized control and digitized/computerized data acquisition is used extensively with these test facilities. Design, parts procurement, and construction of a combined high-frequency oscillating friction and wear and scratch-adhesion tester are underway.

Our surface-characterization equipment includes a state-of-the-art JEOL 840A scanning electron microscope with built-in energy- and wavelength-dispersive X-ray analysis, and an ultramicrohardness tester for in-situ measurements of the hardness of extremely thin films. In addition, we have access to other surface-characterization facilities in the MCT and Materials Science Divisions.

Program Support to DOE Office of Transportation Materials

The Technical Direction and Administrative Program Support project conducts R&D planning; provides project management services required to implement the R&D program; and monitors, evaluates, and provides guidance for contractors funded by the project. Efforts in the past year included preparation of the Annual Operating Plan and Annual Budget; organization of a session for the DOE/OTT Contractor's Coordination Meeting (CCM); and organization and conduct of project review meetings in the three task areas within the tribology program: Engineered Tribological Interfaces, Extreme Environment Lubrication, and Tribology by Design. We organized and conducted a workshop on "Diamond and Diamond-Like-Carbon Films for Transportation Applications" at ANL, with 85 participants representing a wide cross section of the U.S. transportation industry. This workshop resulted in the formulation of some 20 areas of potential applications of diamond and DLC films in the transportation industry. In addition, we participated in extensive technology-transfer activities, including the organization of several sessions for the annual ASME/STLE Tribology conference, the annual STLE conference, and the ICMC conference.

Recent Work by the Tribology Section

Publications

O. O. Ajayi and R. H. Lee, Mechanisms of Wear Flake Formation: As Revealed by the Microscope, presented at INTERMICRO-92, Chicago, July 13-16, 1992.

O. O. Ajayi, A. Erdemir, R. A. Erck, G. R. Fenske, and F. A. Nichols, The Role of Soft (Metallic) Film in Tribological Behavior of Ceramic Materials, Proc. 1991 Intl. Conf. on Wear of Materials, Orlando, FL, April 7-11, 1991, Wear, 149 (1991) pp. 221-232.

O. O. Ajayi, J. H. Hsieh, A. Erdemir, R. A. Erck, and G. R. Fenske, Effect of an Indium Interlayer on the Durability of Silver "Boundary" Film on Silicon Nitride Ceramics, presented at 1992 STLE Annual Mtg., Philadelphia, April 26-30, 1992.

O. O. Ajayi, A. Erdemir, J. H. Hsieh, R. A. Erck, G. R. Fenske, and F. A. Nichols, Boundary Film for Structural Ceramic Materials, to be presented at 9th Intl. Conf. on Wear of Materials, April 13-17, 1993, San Francisco.

O. O. Ajayi, A. Erdemir, R. A. Erck, G. R. Fenske, and F. A. Nichols, The Role of Soft (Metallic) Film in Tribological Behavior of Ceramic Materials, presented at 1991 Intl. Conf. on Wear of Materials, Orlando, FL, April 7-11, 1991.

O. O. Ajayi, A. Erdemir, J. H. Hsieh, R. A. Erck, and F. A. Nichols, Boundary Lubrication of Ceramic Materials by Soft Metallic Coating and Synthetic Oil, presented at 4th Intl. Symp. on Ceramic Materials and Components for Engines, June 10-12, 1991, Goteborg, Sweden.

O. O. Ajayi, A. Erdemir, G. R. Fenske, F. A. Nichols, W. D. Sproul (BIRL, Northwestern U.), M. Graham (BIRL), and P. J. Rudnik (BIRL), Tribological Behavior of Oil-Lubricated, TiN-Coated Steel, presented at Intl. Conf. on Metallurgical Coatings and Thin Films (ICMCTF), April 6-10, 1992, San Diego.

O. O. Ajayi, A. Erdemir, J. Hsieh, and R. H. Lee, Combined Solid and Liquid Lubrication of Ceramic Materials, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

O. O. Ajayi, A. Erdemir, and R. H. Lee, Lubricated Behavior of IBAD-Treated Surfaces, TRIB-ECUT 90/3, Tribology Project Quarterly Progress Report, April-June 1990.

O.O. Ajayi, A. Erdemir, J. H. Hsieh, R. A. Erck, and G. R. Fenske, Combined Solid and Liquid Lubrication of Silicon Nitride at High Temperatures, presented at 991 Ann. STLE Mtg., April 24-May 3, 1991, Montreal.

C. C. Cheng, R. A. Erck and G. R. Fenske, Microstructural Studies of IAD and PVD Cr Coatings by Cross Section Transmission Electron Microscopy, presented at Materials Research Society 1988 Fall Mtg., Boston, Nov. 28-Dec. 3, 1988, pp. 177-182.

R. A. Erck and F. A. Nichols, Practical Uses of Ion Beams for Surface Coating and Modification, INVITED TALK to be presented at 1992 TMS Fall Mtg., Nov. 1-5, 1992, Chicago.

R. A. Erck, A. Erdemir, G. R. Fenske, and J. H. Hsieh, Ion-Beam-Assisted Surface Modifications for Friction and Wear Reduction, *Lubrication Engineering* Vol. 48, April 1991, pp. 307-317.

R. A. Erck and L. E. Rehn, Correction of Energy Shift during RBS Data Analysis: Application to Study of Solute Segregation in Mo-Re Alloys, *Nuclear Instruments and Methods in Physics Research B62* Elsevier Sci. Publishers, (1991) pp. 143-146.

R. A. Erck, C. M. Wayman (U. of Illinois at Urbana-Champaign), and L. E. Rehn, Radiation-Induced Segregation and Precipitation in Molybdenum-Rhenium Alloys, Published in *Radiation-Induced Changes in Microstructure: 13th Intl. Symp. (Part I)*, ASTM STP 955, eds. F. A. Garner, N. H. Packan, and A. S. Kumar, Amer. Soc. for Testing and Materials, Philadelphia, 1987, pp. 721-729.

R. A. Erck, G. R. Fenske, A. Erdemir, J. H. Hsieh, and O. O. Ajayi, Properties of Hard Boron Nitride Films Produced by Ion-Beam-Assisted Deposition, *Proc. Surface Modification of Metals by Ion Beams-91 Mtg.*, July 15-19, 1991, Washington, DC.

R. A. Erck, A. Erdemir, O. O. Ajayi, G. R. Fenske, and J. H. Hsieh, Tribological Properties of Ion-Beam-Bombarded Oxide Coatings on Steel, presented at Intl. Conf. on Metallurgical Coatings and Thin Films, April 6-10, 1992, San Diego.

R. A. Erck, J. H. Hsieh, and G. R. Fenske, Effect of Ion Bombardment on Adhesion of Silver to Silicon Nitride, *Proc. Materials Research Society 1992 Spring Mtg.*, April 27-May 1, 1992, San Francisco, p. 242.

R. A. Erck, Weibull Statistics Applied to Fracture of a Metal-Ceramic Interface, ANL/OTM-91/1 Quarterly Progress Report DOE-OTM Tribology Program, Jan.-March 1991.

R. A. Erck, G. R. Fenske, and J. H. Hsieh, IBAD Chamber Modifications, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

R. A. Erck and R. H. Lee, Investigations of RIBAD Boron Nitride, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

R. A. Erck, G. R. Fenske, and J. Hsieh, IBAD Process Development, TRIB-ECUT 90/3 Tribology Project Quarterly Progress Report, April-June 1990.

R. A. Erck, IBAD Process Characterization, TRIB-ECUT 90/3 Tribology Project Quarterly Progress Report, April-June 1990.

A. Erdemir, R. A. Erck, and J. Robles (U. of California), The Relation of Hertzian Contact Pressure to Friction Behavior of Self-Lubricating Boric Acid Films, Proc. 18th Intl. Conf. on Metallurgical Coatings and Thin Films, April 22-26, 1991, San Diego, Surface and Coatings and Coatings Tech., 49 (1991) pp. 435-438.

A. Erdemir, O. O. Ajayi, R. A. Erck, G. R. Fenske, and F. A. Nichols, Synergistic Effects of Solid Lubricants on the Boundary-Lubrication Behavior of Ceramics Lubricated with Synthetic Lubricants, presented at 1992 Coatings for Advanced Heat Engines Workshop, Aug. 2-7, 1992, Monterey, CA.

A. Erdemir, F. A. Nichols, G. R. Fenske, and J. H. Hsieh, Sliding Friction and Wear of Ceramics with and without Soft Metallic Films, MSR Bulletin, Vol. XVI, No. 10, Oct. 1991, pp. 49-53.

A. Erdemir, O. O. Ajayi, G. R. Fenske, R. A. Erck, and J. H. Hsieh, The Synergistic Effects of Solid and Liquid Lubrication on the Tribological Behavior of Transformation Toughened ZrO_2 Ceramics, Proc. of ASME/STLE Joint Tribology Conf., Oct. 14-16, 1991, St. Louis, STLE Tribology Transactions Vol. 35 (1992), pp. 287-297.

A. Erdemir, O. O. Ajayi, R. A. Erck, and G. R. Fenske, Effect of Synthetic Lubricants on Tribological Properties of Surface-Modified Ceramics, Proc. Annual Automotive Technology Development Contractors' Coordination Mtg., Oct. 28-31, 1991, Dearborn, MI.

A. Erdemir, O. O. Ajayi, and R. A. Erck, Effect of Ambient Temperature on the Lubricity and Self-Lubricating Mechanisms of Boric Acid, Proc. 1992 Ann. STLE Mtg., May 4-7, 1992, Philadelphia, p. 34.

A. Erdemir, G. R. Fenske, R. A. Erck, and C. C. Cheng, Adhesion and Tribological Characteristics of IAD Silver Coatings on Alumina Ceramics, presented at 1989 Fall Mtg. TMS, Oct. 1989, Indianapolis.

A. Erdemir, D. E. Busch, J. H. Hsieh, and R. A. Erck, Effect of Silver Coatings on Tribological Characteristics of Si_3N_4 in Dry and Humid Air, presented at 1991 STLE Mtg., April 24-May 2, 1991, Montreal, p. 26.

A. Erdemir, R. A. Erck, and J. Robles (U. of Calif.), Solid Lubricating Characteristics of Boric Acid Forming Surfaces in Various Test Environments, 1991 STLE Mtg., April 24-May 2, 1991, Montreal.

A. Erdemir, O. O. Ajayi, G. R. Fenske, R. A. Erck, and J. H. Hsieh, Tribology of Solid and Liquid Lubricated ZrO_2 Ceramics, ANL/OTM-91/1 Quarterly Progress Report DOE-OTM Tribology Program Jan.-March 1991.

A. Erdemir, R. A. Erck, and J. Robles (U. of California), The Relation of Hertzian Contact Pressure to Friction Behavior of Self-Lubricating Boric Acid Films, Proc. Intl. Conf. on Metallurgical Coatings and Thin Films, San Diego, April 22-26, 1991, pp. A-96.

A. Erdemir, R. A. Erck, and J. Robles, Tribological Characterization of Self-Lubricating Boric Acid Films, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

A. Erdemir, R. A. Erck, and G. R. Fenske, IBAD Tribological Characterization, TRIB-ECUT 90/3 Tribology Project Quarterly Progress Report, April-June 1990.

A. Erdemir, M. Switala (Franklin and Marshall College), R. Wei (Colorado State U.), and P. Wilbur (CSU), A Tribological Investigation of the Graphite-to-Diamond-Like Behavior of Amorphous Carbon Films Ion-Beam-Deposited on Ceramic Substrates, presented at 18th Intl. Conf. on Metallurgical Coatings and Thin Films, San Diego, April 22-26, 1991; published in Surface and Coatings Technology, 50 (1991) pp. 17-23.

A. Erdemir, R. A. Erck, G. R. Fenske, and F. A. Nichols, High-Temperature Tribological Characteristics of Silver and Gold Coatings on Ceramics Prepared by Ion-Beam Assisted Deposition, INVITED PAPER presented at China Intl. Symp. for Youth Tribologists, Aug. 10-14, 1992, Lanzhou, China.

A. Erdemir, Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part I: Crystal Chemistry and Self-Lubricating Mechanism of Boric Acid, Proc. 45th Ann. Mtg. of Soc. of Tribologists and Lubrication Engineers, Denver, May 7-10, 1990, Lubr. Eng., Vol. 47, 3, pp. 168-173.

A. Erdemir, G. R. Fenske, R. A. Erck, F. A. Nichols, and D. Busch, Tribological Properties of Boric Acid and Boric-Acid-Forming Surfaces. Part II: Mechanisms of Formation and Self-Lubricating of Boric Acid Films on Boron- and Boric Oxide-Containing Surfaces, Proc. 45th Ann. STLE Mtg., Denver, May 7-10, 1990, STLE Preprint No. 90-AM-3E-2.

G. R. Fenske and R. A. Erck, Ion Beams 'Nail' Thin Films, Ceramic Industry, Vol. 136, No. 3, March 1991, by Business News Publ. Co., Troy, MI.

G. R. Fenske, Ion-Beam-Assisted Deposition of Lubricious Compounds, ANL/OTM-91/1, Quarterly Progress Report DOE-OTM Tribology Program, Jan.-Mar. 1991.

G. R. Fenske and R. H. Lee, SEM Characterization of Worn Ag-Coated Piston Rings, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

G. R. Fenske, Ion-Beam-Assisted Deposition of Lubricious Compounds, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

G. R. Fenske, Engineered Tribological Interfaces, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

G. R. Fenske, R. Hu, R. A. Erck, A. Erdemir, and R. H. Lee, Ion-Beam Mixing of Lubricious Layers on Metallic Alloys, TRIB-ECUT 90/3 Tribology Project Quarterly Progress Report, April-June 1990.

G. R. Fenske, Ion-Beam-Assisted Deposition of Lubricious Compounds, Tribology Project Quarterly Progress Report, April-June 1990, TRIB-ECUT 90/3

G. R. Fenske, Engineered Tribological Interfaces, TRIB-ECUT 90/3, Tribology Project Quarterly Progress Report, April-June 1990.

M. R. Fox, A. B. Hull, J.-H. Park, J.-H. Hsieh, and G. Dragel, Corrosion and Electrical Properties of Ceramic Insulators after Exposure to Flowing Lithium at 400°C, Contribution to Fusion Reactor Materials Semiannual Progress Report for Period Ending Mar. 31, 1991, Report No. DOE-ER/0313/10; published by ORNL.

N. A. Henein (Wayne State U.) and G. R. Fenske, Measurement of the IFT of Ag-Coated Rings, ANL/OTM-91/1, Quarterly Progress Report DOE-OTM Tribology Program Jan.-Mar. 1991.

J. H. Hsieh, R. A. Erck, G. R. Fenske, and F. A. Nichols, Metallic Seal-Coating Applied on Zirconia Thermal-Barrier Coating, presented at Intl. Conf. on Metallurgical Coatings and Thin Films, April 6-10, 1992, San Diego.

J. H. Hsieh, D. E. Busch, R. A. Erck, G. R. Fenske, and F. A. Nichols, Investigation of Titanium Nitride Films Prepared by Ion-Beam-Assisted Deposition at High Ar⁺/Ti Ratio, presented at 1992 MRS Spring Mtg., April 27-May 1, 1992, San Francisco.

J. H. Hsieh, O. O. Ajayi, A. Erdemir, R. A. Erck, and G. R. Fenske, Adhesion Degradation of Ag and Nb Films Deposited on ZrO₂ by IBAD after Exposure at 250°C, ANL/OTM-91/1 Quarterly Progress Report DOE-OTM Tribology Program Jan.-March 1991.

J. H. Hsieh, R. H. Lee, R. A. Erck, G. R. Fenske, Y. Y. Su, M. Marek, and R. F. Hochman (Soc. of Mat. Eng., Georgia Institute of Technology), Niobium Coatings on 316L Stainless Steels for Improving Corrosion Resistance, Proc. Intl. Conf. on Metallurgical Coatings and Thin Films, San Diego, April 22-26, 1991, pp. A-16.

J. H. Hsieh, D. Bush, R. A. Erck, and G. R. Fenske, AES Investigation of Titanium Nitride Films Prepared by Ion-Beam-Assisted Deposition at High Ar⁺/Ti Ratio, ANL/OTM-90/2, Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990.

A. B. Hull, M. R. Fox, and J.-H. Hsieh, Vanadium-Base-Alloy Surface Modification for Liquid Metal Blankets and First-Wall in Magnetic Fusion Reactors, presented at 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

P. S. Maitya, S. F. Zentack, D. Singh, D. S. Poa (CMT), D. E. Busch, and R. B. Poeppel, Evaluation of Tribocor 532N as a Container Material for Pyrochemical Applications, to be presented at 1992 TMS Fall Mtg., Chicago, Nov. 1-5, 1992.

R. H. Lee, High Temperature Lubrication, presented at Meeting of Society of Experimental Mechanics, Urbana, IL, March 31, 1992.

R. H. Lee, The Growth of Synthetic Diamond Crystals and Films, presented at INTER/MICRO-92, Chicago, July 13, 1992.

R. H. Lee, Evaluating Daguerreotypes, presented at INTER/MICRO-92, Chicago, July 14, 1992.

F. A. Nichols, Guest Editor, What is Tribology, Anyway?, MSR Bulletin, Vol. XVI, No. 10, Oct. 1991, pp. 30-32.

F. A. Nichols, ed., G. R. Fenske, R. A. Erck, J. H. Hsieh, M. Switala, R. Wei, O. O. Ajayi, A. Erdemir, Quarterly Progress Report DOE-OTM Tribology Program, Apr.-June 1991, ANL/OTM-91/2.

F. A. Nichols and A. I. Michaels, eds., Quarterly Progress Report DOE-OTM Tribology Program, Jan.-Mar. 1991, ANL/OTM-91/1.

F. A. Nichols and A. I. Michaels, eds., Quarterly Progress Report DOE-OTM Tribology Program, Oct.-Dec. 1990, ANL/OTM-90/2.

F. A. Nichols and A. I. Michaels, eds., Quarterly Progress Report DOE-ECUT Tribology Program, TRIB-ECUT 90/2.

F. A. Nichols and A. I. Michaels, eds., Quarterly Progress Report DOE-ECUT Tribology Program, April-June 1990, TRIB-ECUT 90/3.

Patent

A. Erdemir, O. O. Ajayi, G. R. Fenske, and R. A. Erck, Combination of Silver and Synthetic Oil as Lubricant for High-Temperature Ceramics. Patent application submitted June 21, 1991.

Irradiation Performance

Section Manager: L. A. Nelmark

Principal Investigators: A. G. Hins, D. D. Keiser,¹ Y. Y. Liu, H. Tsai

Support Staff: A. B. Cohen, D. A. Donahue, J. E. Sanecki, T. L. Shearer

Salaried Staff and Technicians: D. J. Evans, W. C. Kettman, F. Pausche, Jr.,

D. O. Pushis, F. E. Savole

Secretary: E. L. Hartig

Visiting Scientist: K. Hirai²

The principal objective of the programs in this Section is to determine and assess the behavior of materials, principally fuels and claddings, in the core environment of nuclear reactors, and to identify research and development areas as necessary. This environment results in neutron damage and chemical, metallurgical, and mechanical processes that occur at high temperatures. The Section's present activities focus on fuel development for liquid-metal-cooled reactors and on characterization of irradiated materials from light-water reactors. The Section operates the Alpha-Gamma Hot Cell Facility (AGHCF) and the Irradiated Materials Laboratory (IML), in which it conducts postirradiation examinations and investigations.

Fuel Development

Integral Fast Reactor

The Integral Fast Reactor (IFR) program is ANL's initiative for development of an inherently safe liquid-metal-cooled reactor (LMR) in combination with an integral fuel-reprocessing facility. The fuel cycle is based on U-Pu-Zr alloy fuel, a system first explored at ANL in the 1960s. The Section's current activities include lead responsibilities for prototype fuel-rod irradiation tests completed in the Fast Flux Test Facility (FFTF); a fuel-design variables test, a cladding materials test and a series of transient overpower tests in EBR-II; and investigation of irradiated and unirradiated fuel/cladding compatibility under off-normal conditions. The tests on unirradiated materials are intended to elucidate the behavior of the irradiated materials. The Section also performs destructive examination of EBR-II fuel rod experiments for the ANL Fuels and Engineering Division. Also, a joint effort with the Reactor Engineering Division is investigating the behavior of whole irradiated fuel pins under simulated off-normal conditions in the AGHCF. The Section also assists in fuel/cladding compatibility studies conducted by the Chemical Technology Division. The IFR is expected to account for a significant fraction of the Section's activities for the foreseeable future.

¹Programmatically assigned from Fuels and Engineering Division.

²Japanese Power Reactor and Nuclear Fuel Development Corporation.

Advanced Oxide Transient Performance

The purpose of this LMR program is to investigate the transient overpower performance of advanced oxide fuel pin designs at slow ramp rates. This is a cooperative program between DOE and the Japanese Power Reactor and Nuclear Fuel Development Corporation. The program uses the unique capability of the EBR-II reactor for whole-core overpower events at slow ramp rates of 0.01 to 10%/s. Phase II of the program, begun in September 1987, highlights advanced alloys for oxide fuels and is expected to be a seven-year effort. The Section's role is to conduct three transient overpower tests in EBR-II, conduct a series of whole-pin transient heating tests in the AGHCF, and perform all postirradiation examinations for the program's three experimenters in the AGHCF. The first of the overpower tests was conducted in early 1992, and the transient heating tests are expected to begin before the end of 1992.

Characterization of Irradiated Materials

TMI-2 Lower Head Examination

The NRC, with support from a consortium of foreign countries, is completing a program on evaluating the margin-to-failure of the TMI lower head during the 1979 accident. Samples removed from the lower head for metallurgical evaluation included 13 instrument tube nozzles, 6 of which were sent to the Irradiation Performance Section for detailed examinations. The purpose of these examinations was to provide the accident analysts with data to use in their thermomechanical analysis of the lower head conditions. The findings at ANL were instrumental in identifying what was likely an initial layer of control assembly materials deposited on the lower head before the arrival of the significant molten fuel mass later in the accident. This and other ANL findings have provided the analysts with a basis for generating the accident scenario for the lower head that is required for their margin-to-failure analysis. This work was completed in 1992, and future work in this area will be advisory only.

Ancillary Activities

The Irradiation Performance Section is continuing its cooperative program with the Reactor Engineering Division on understanding the behavior of fuel and target materials for the potential Heavy-Water New Production Reactor, albeit at a significantly reduced level. This program has undergone drastic budget reductions in light of world events. The current emphasis is on the swelling behavior of tritium target samples tested in our Fuel Behavior Test Apparatus (FBTA). The present view is that the program will continue only into 1993.

The Section is continuing its involvement with the Corrosion Section in the NRC's Irradiation-Assisted Stress Corrosion Cracking Program for LWR stainless steel components. Our efforts provide the investigators with the necessary fractographic (SEM) and microchemical (Auger microprobe) data for evaluating the phenomenon.

The Section is maintaining its involvement in the Laboratory's space power initiative by providing expert consulting on the behavior and potential of cermet fuels. This low-level activity could expand into an irradiation program in either TREAT or EBR-II or both.

We are increasing our activity in the Fusion Power Program now that the materials irradiation program appears to be moving from the FFTF to EBR-II. Our involvement initially will be to assist the ANL experimenters with our knowledge of experimental procedure in EBR-II.

Lastly, the Irradiation Performance Section continues to support the development of U_3Si_2 fuel for the Advanced Neutron Source Reactor at Oak Ridge National Laboratory. The capabilities of the AGHCF in characterizing irradiated materials are being used in this program.

Recent Work by the Irradiation Performance Section

Publications

A. Boltax (React. Mat. Tech.), L. A. Neimark, H. Tsai, M. Katsuragawa (PNC, Japan), and S. Shikakura (PNC), Reliability of Fast Reactor Mixed-Oxide Fuel during Operational Transients, submitted to Intl. Conf. on Fast Reactor and Its Related Fuel Cycles (FR '91), Kyoto, Japan, Oct. 28-Nov. 1, 1991.

H. M. Chung, J. E. Sanecki, W. E. Ruther, and T. F. Kassner, Irradiation-Induced Modification of Grain-Boundary Microchemistry in Stainless Steels, to be presented at Symp. on Microstructures and Mechanical Properties of Aging Materials, TMS-AIME Fall Mtg., Nov. 1-5, 1992, Chicago.

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Stress Corrosion Cracking Susceptibility of Irradiated Type 304 Stainless Steels, presented at 16th Intl. Symp. on Effects of Radiation on Materials, June 21-25, 1992, Denver.

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Irradiation-Induced Sensitization and Stress Corrosion Cracking of Type 304 Stainless Steel Core-Internal Components, presented at 5th Intl. Symp. on Degradation of Materials in Nuclear Power Systems-Water Reactors, Aug. 25-29, 1991, Monterey, CA.

H. M. Chung, W. E. Ruther, J. E. Sanecki, and T. F. Kassner, Understanding Susceptibility of In-Core Components to Irradiation-Assisted Stress Corrosion Cracking, submitted to Amer. Nucl. Soc. Intl. Top. Mtg. on Safety of Thermal Reactors, July 21-25, 1991, Portland, OR.

H. M. Chung, T. F. Kassner, J. Y. Park, W. E. Ruther, J. E. Sanecki, W. J. Shack, and W. K. Soppet, Environmentally Assisted Cracking in Light Water Reactors (condensed version), to be published in Compilation of Contract Research for the Materials Engineering Branch Division of the NRC, Engineering Annual Report for FY 1990, NUREG-0975, Vol. 8.

H. M. Chung, T. F. Kassner, W. J. Shack, W. E. Ruther, J. Y. Park, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-Sept. 1990, NUREG/CR-4667 Vol. 11, ANL-91/9 (1991).

D. R. Diercks and L. A. Neimark, TMI-2 Vessel Investigation Project (VIP) Metallurgical Program, to be published in NRC Div. of Engineering Mater. Engineering Branch Annual Report, Jan. 1991.

A. G. Hins, R. F. Simandl (Oak Ridge Y-12 Plant), L. R. Walker (Oak Ridge Y-12), H. L. Richards (Oak Ridge Y-12), and A. E. Knox (EP), A Study of Core/Cladding Bonding in IPNS Booster Target Discs, Proc. 2nd Intl. Conf. on Hot Isostatic Pressing-Theory and Applications, Gaithersburg, MD, ASM Intl., Materials Park, OH., eds. R. J. Schaefer and M. Linzer, June 7-9, 1989, pp. 281-291.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, presented at NRC Aging Res. Info. Conf., March 24-27, 1992, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, W. K. Soppet, and W. J. Shack, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report April-September 1991, NUREG/CR-4667, Vol. 13, ANL-92/6 (1992).

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, A. G. Hins, J. Y. Park, and W. J. Shack, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, INVITED PAPER presented at 19th Water Reactor Safety Information Mtg., Rockville, MD, Oct. 28-30, 1991.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, presented at 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Rockville, MD.

T. F. Kassner, W. E. Ruther, H. M. Chung, P. D. Hicks, J. Y. Park, W. J. Shack, and A. G. Hins, Fatigue and Environmentally Assisted Cracking in Light Water Reactors, Proc. 19th Water Reactor Safety Information Mtg., Oct. 28-30, 1991, Bethesda, MD, NUREG/CP-0119, Vol. 1, pp. 127-150.

W. J. Shack, P. D. Hicks, W. E. Ruther, H. M. Chung, T. F. Kassner, W. K. Soppet, and J. E. Sanecki, Environmentally Assisted Cracking in Light Water Reactors - Semiannual Report. October 1990-March 1991, NUREG/CR-4667, Vol. 12, ANL-91/24 (1991).

H. Tsai, L. A. Neimark, T. Asaga (PNC, Japan), and S. Shikakura (PNC), Performance of Fast Reactor Mixed-Oxide Fuel Pins during Extended Overpower Transients, to be published in Proc. 11th Intl. Conf. on Structural Mechanics in Reactor Technology (SMIRT), Aug. 18-23, 1991, Tokyo.

H. C. Tsai and L. A. Neimark, Irradiation Performance of Full-length Metallic IFR Fuels, submitted to Intl. Conf. on Design and Safety of Advanced Nucl. Power Plants (ANP '92), Oct. 25-29, 1992, Tokyo.

H. C. Tsai, Y. Y. Liu, D. Y. Wang (National Chung Hsing U., Taiwan), and J. M. Kramer (RE), Behavior of Low-Burnup Metallic Fuels for the Integral Fast Reactor at Elevated Temperatures in Ex-Reactor Tests, submitted to Intl. Conf. on Fast Reactors and Related Fuel Cycles (FR'91), Oct. 28-Nov. 1, 1991, Kyoto, Japan.

Patents

H. C. Tsai, Vanadium Mold for Casting Metallic Fuel Slugs for Fast Reactor Applications. Patent application submitted June 20, 1991.

H. C. Tsai and L. A. Neimark, Vanadium-lined Cladding Tubes for Fast Reactor Applications. Patent application submitted May 2, 1991.

Components Technology

Superconductivity Applications

Principal Investigators: Y. S. Cha, T. M. Mulcahy, R. C. Niemann,
K. L. Uherka

Secretary: J. A. Stephens

Visiting Scientists: F. C. Moon,¹ T. D. Rossing²

Students: J. Almer,³ C. Gabrys,⁴ S. Y. Seol,⁵ A. Unal⁵

The special properties of superconducting materials allow many unique applications whose importance has increased significantly with the discovery several years ago of materials that superconduct at temperatures above the boiling point of nitrogen. The Superconductivity Applications Section conducts research and development on new applications of superconductivity and its support technologies. The work is both experimental and analytical.

Many of the Section's projects are funded by the Superconductivity Pilot Center at ANL; such projects are conducted with industrial collaborators, typically with each institution funding its own work but with staff from each institution working on the same project. Section members are thus frequently involved with industrial scientists and engineers in these collaborative programs. The Section collaborates closely with the MCT Ceramics Section in fabricating experimental superconducting devices, and with members of the ANL Energy Systems Division in developing magnetically levitated ground transport (maglev) systems.

Cryostat Current Leads

A cryostat current lead provides power from room-temperature sources to devices operating at liquid helium temperatures. Early experimental work in collaboration with the Westinghouse Science and Technology Center resulted in a high-temperature superconductor (HTS) lead that superconducted 2 kA, while helium boil-off from the lead was less than that of the minimum obtained by the best theoretical lead made entirely of a normal conductor. Since then, we have constructed a lead test apparatus with a very low background heat leak of 5 mW. This apparatus is shown on the next page. This apparatus should allow testing of a pair of HTS leads with 100 A current and with less than one-tenth the boil-off of a conventional lead.

¹Cornell University.

²Northern Illinois University.

³University of Illinois at Chicago.

⁴University of Vermont.

⁵Texas Tech University.

Test apparatus for cryostat current leads

We are presently collaborating with three different companies in the HTS leads area. Ceracon is producing the HTS component via a unique sintering process. Intermagnetics General is interested in HTS leads for their commercial magnets. Superconductivity, Inc., is interested in HTS leads for its superconducting magnetic energy storage (SMES) devices.

Based on early experimental results from our test apparatus and on recent analyses of lead performance, we have discovered that the ratio of helium vapor-density/liquid-density provides a significant modification to the relationship between heat input and vapor mass flow. We have also shown theoretically that a minimal boil-off exists for self-cooled leads and that an intermediate-temperature heat sink is needed to reduce the boil-off below this limit. In addition, we have applied for a patent on a unique design for a HTS lead, and this invention has been licensed to Illinois Superconductor Corporation.

Magnetic Bearings

For several years, a collaborative project with the United Technologies Research Center (UTRC) has explored the use of HTSs in magnetic bearing applications. We have also recently initiated a collaborative project with H1-T_c Superconco to characterize the properties of their HTS samples in order to improve levitation properties for magnetic bearings.

In the UTRC project, we have demonstrated an HTS bearing with a rotational drag that is one order of magnitude lower than that of a conventional magnetic bearing and several orders of magnitude lower than that of mechanical bearings. With this bearing, an energy-efficient flywheel could be constructed with a bearing drag loss of less than 2%/day. Such a flywheel has the potential for use in diurnal utility energy storage or as a replacement for batteries in an electric vehicle. We are now marketing a proposal to develop this flywheel technology. A patent on this bearing/flywheel concept will be granted soon, and the invention has been licensed to United Technologies.

A vacuum-chamber apparatus has been developed at ANL to further test the rotational losses of HTS bearings. We have identified several design improvements to further reduce loss, and we expect to test these designs in rotors of increasing size.

Fault-Current Limiter

We have invented an HTS fault-current limiter (FCL) that operates as a nonlinear resistor. A patent application has been filed and we have licensed the invention to Illinois Superconductor Corporation. A small model of this FCL has been built and successfully operated at ANL.

HTS Magnet Stabilization

We have recently invented a new type of stabilization for HTS magnets. When operated at a temperature above 20 K, HTSs are expected to have difficulties if a perturbation results in a normal zone, because the propagation velocity of the normal zone is several orders of magnitude lower than in low-temperature superconductors. All of the heat will be dissipated locally and the magnet may then burn out. Thus, with conventional superconductor magnet design, even if we had an HTS with high current density, HTS magnets would be unreliable. We have used microchannel heat exchanger techniques to design HTS magnet concepts that are cryostable using subcooled liquid cryogenes. Once HTS conductors with useful current density become available, HTS magnets should be stable and reliable using this design. We hope to test this design concept experimentally in the near future.

HTS Undulator

We have recently initiated a project with the Advanced Photon Source at ANL to investigate the use of HTS components as undulators and insertion devices to produce synchrotron radiation. In this application, the HTS acts as a diamagnetic material that responds to beam dynamics. It offers several unique advantages over conventional permanent magnet or coil-type undulators and has the potential to produce very-short-wavelength, high-intensity X-rays. The present work has consisted of analysis. We hope to commence experimental work on this HTS application in the near future.

Maglev

The Section is collaborating with members of ANL's Energy Systems Division in the development of maglev systems, as part of a federal government program to evaluate this technology. One project utilizes a rotating-wheel test facility, shown in the photograph below, on which experimental models of maglev vehicles are levitated over guideways mounted on the wheel in order to test levitation properties and vehicle dynamics. We have also been beta-testing a new finite-element computer code (ELEKTRA from Vector Fields Ltd.) that analyzes three-dimensional eddy currents with moving conductors. A number of experiments have been conducted on the wheel and used to verify the results of the code. With ELEKTRA, we should be able to evaluate a number of maglev designs not previously amenable to analysis.

Test wheel used to examine maglev system properties and dynamics

Recent Work by the Superconductivity Applications Section

Publications

U. Balachandran, T. Suratwala, C. A. Youngdahl, J. R. Hull, R. B. Poeppel, V. Dravid (Northwestern U.), and L. D. Marks (NU), Processing, Microstructure, and Properties of Quench-Melt-Grown YBCO Superconductors, presented at 1992 TMS Annual Mtg., Symposium on High T_c Superconductivity in Bulk, San Diego, March 1-5, 1992.

Y. Cai, S. S. Chen, and T. M. Mulcahy, Fluidelastic Instability of Loosely Supported Tubes, presented at 9th Symp. on Energy Engineering Sciences, Argonne National Laboratory, May 13-15, 1991.

Y. S. Cha, Analysis of Magnetic Energy Stored in Superconducting Coils with and without Ferromagnetic Inserts, to be presented at 37th Annual Conf. on Magnetism and Magnetic Materials, Houston, Dec. 1-4, 1992.

Y. S. Cha, R. C. Niemann, and J. R. Hull, Thermodynamic Analysis of Helium Boil-off Experiments with Pressure Variations, submitted to Cryogenics.

Y. S. Cha, J. R. Hull, and U. S. Choi, Cryostabilization of High Temperature Superconducting Magnets Using Subcooled Flow in Microchannels, presented at 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

Y. S. Cha, S. E. Dorris, J. R. Hull, and R. B. Poeppel, The Effect of Processing Parameters during Heat Treatment of Bulk High-T_c Superconductors, INVITED PAPER: Proc. 1991 ASME Winter Annual Mtg., Session on Bulk Processing and Mechanical Properties of High-T_c Superconductors, Atlanta, Dec. 1-6, 1991, The American Society of Mechanical Engineers, New York, 1992, 91-WA-AES-3, pp. 1-9.

Y. S. Cha, John R. Hull, Thomas M. Mulcahy, and Thomas D. Rossing (Northern Illinois U.), Effect of Size and Geometry on Levitation Force Measurements Between Permanent Magnets and High-Temperature Superconductors, submitted to 5th Joint MMM-Intermag Conf., Pittsburgh, June 18-21, 1991; J. Appl. Phys., Vol. 70, No. 10, Pt II, pp. 6504-6506, Nov. 1991.

C. Gabrys (U. of Vermont), J. R. Hull, and T. M. Mulcahy, A High-Speed Demonstration Motor with Superconducting Bearings, submitted to Amer. J. of Phys.

K. C. Goretta, W. Wu, C. T. Wu, D. Xu, C. A. Youngdahl, D. Shi (MSD), J. P. Singh, J. J. Picciolo, M. T. Lanagan, J. R. Hull, J. T. Dusek, S. E. Dorris, N. Chen (MSD), A. C. Biondo, U. Balachandran, and R. B. Poeppel, High-T_c Superconductors: Fabricating Technologies and Future Perspectives, Mater. Chem. and Phys., 31 (1992), pp. 73-78.

J. R. Hull, High-Temperature Superconducting Current Leads, submitted to IEEE Trans. Appl. Supercond. via Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

J. R. Hull and K. L. Uherka, Recent Advances in High-Temperature Superconductor Wire Fabrication and Applications Development, presented at 1992 Intersociety Energy Conversion Engineering Conf., San Diego, Aug. 3-7, 1992.

J. R. Hull and R. B. Poeppel, Development of High-Temperature Superconductor Applications at Argonne National Laboratory, presented at 1992 TCSUH Workshop on HTS Materials, Bulk Processing, and Bulk Applications, Houston, Feb. 27-28, 1992.

J. R. Hull, A. Unal (Texas Tech U.) and M.-C Chyu (TTU), Analysis of Self-Cooled Binary Current Leads Containing High-Temperature Superconductors, to be published in *Cryogenics*.

J. R. Hull, Potential for Use of High-Temperature Superconductors in Fusion Reactors, to be published in Proc. 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

J. R. Hull, D. M. Rote (ES), and H. T. Coffey (ES), Superconductivity and Maglev Transportation, Hybrid Circuit Technology, Vol. 8(91), Sept. 1991, pp. 22-25.

J. R. Hull, T. M. Mulcahy, K. Salama (U. of Houston), B. R. Weinberger (United Technologies Research Ctr.), and L. Lynds (UTRC), Magnetic Levitation and Stiffness in Melt-Textured Y-Ba-Cu-O, to be published in J. of Appl. Phys..

John R. Hull, Susan M. Schoenung (W. J. Schafer Assoc.), David N. Palmer, and Mark K. Davis (ABB, Inc.), Design and Fabrication Issues for Small-Scale SMES, INVITED PAPER , CB-1, presented at Cryogenic Engineering Conf., Huntsville, AL, June 11-14, 1991.

J. R. Hull and J. He (ES), Maglev System Concept Using 20 K High-Temperature Superconductors, submitted to Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

John R. Hull, Potential for Use of High-Temperature Superconductors in Fusion Reactors, presented at 5th Intl. Conf. on Fusion Reactor Materials, Clearwater, FL, Nov. 17-22, 1991.

John R. Hull and Jianliang He, Maglev System Concept Using 20-K High-Temperature Superconductors and Hyperconductors, presented at Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

T. M. Mulcahy, J. R. Hull, J. D. Almer, and T. D. Rossing (Northern Illinois U.), Edge Effects on Forces and Magnetic Fields Produced by a Conductor Moving Past a Magnet, presented at Intl. Magnetism Conf. (Intermag '92), St. Louis, April 13-16, 1992; to be published in IEEE Transactions on Magnetism.

T. M. Mulcahy, T. D. Rossing (Northern Illinois U.), J. R. Hull, and J. Almer, Edge Effects on Forces and Magnetic Fields Produced by a Conductor Moving Past a Magnet, presented at Intl. Magnetism Conf. (Intermag '92), St. Louis, April 13-16, 1992, sponsored by Magnetism Soc. of IEEE.

T. M. Mulcahy, T. D. Rossing (Northern Illinois U.), and J. He, Forces on a Magnet Moving Past Figure-Eight Coils, presented at Intl. Magnetism Conf. (Intermag '92), St. Louis, April 13-16, 1992, sponsored by Magnetism Soc. of IEEE.

R. C. Niemann, Y. S. Cha, and J. R. Hull, Performance Measurements of Superconducting Current Leads Having Low Helium Boiloff Rates, presented at 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

D. N. Palmer and M. K. Davis (ABB, INC.), J. R. Hull, and S. M. Schoenung (W. J. Schafer Assoc.), Engineering and Economic Realities of High-Temperature SMES, submitted to Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

R. B. Poeppel, K. C. Goretta, U. Balachandran, I. Bloom, Y. S. Cha, S. E. Dorris, J. T. Dusek, J. E. Emerson, K. E. Gray, M. C. Hash, J. R. Hull, J. S. Kallend, R. T. Kampwirth, M. A. Kirk, D. S. Kupperman, M. T. Lanagan, V. A. Maroni, R. L. McDaniel, D. J. Miller, J. J. Picciolo, J. L. Routbort, J. P. Singh, and C. A. Youngdahl, Practical Superconductor Development for Electrical Power Applications - Annual Report for FY 1991, ANL-91/28 (1991).

R. B. Poeppel, U. Balachandran, T. Suratwala, C. A. Youngdahl, J. R. Hull, and V. David (Northwestern U.), Processing and Properties of Quench-Melt-Grown YBCO Superconductors, INVITED PAPER presented at 44th Pacific Coast Regional Mtg. of Am. Ceram. Soc., Oct. 31-Nov. 2, 1991, San Diego.

T. D. Rossing (Northern Illinois U.) and J. R. Hull, Magnetic Levitation, submitted to The Physics Teacher.

Thomas D. Rossing (Northern Illinois U.), Rodney Korte (NIU), and John R. Hull, Effect of Guideway Discontinuities on Magnetic Levitation and Drag Forces, 5th Joint MMM-Intermag Conf., Pittsburgh, June 18-21, 1991, J. Appl. Phys. 70 (10), Nov. 1991, pp. 6507-6509.

S. Y. Seol, M.-C. Chyu (Texas Tech U.), T. M. Kuzay, and J. R. Hull, Minimization of Refrigeration Power Requirements for Mechanical Supports in Cryogenic Systems, submitted to Cryogenics

S. Y. Seol, M. -C. Chyu (Texas Tech U.), T. M. Kuzay, and J. R. Hull, Minimization of Refrigeration Power Requirements for Mechanical Supports in Cryogenic Systems, submitted to Intersociety Energy Conversion Engineering Conference, Boston, Aug. 4-9, 1991.

K. L. Uherka, Superconductivity - Past, Present and Future, presented at 54th Annual American Power Conf., Chicago, April 15, 1992.

B. R. Weinberger and L. Lynds (United Technologies Research Ctr.), J. R. Hull and U. Balachandran, Low Friction in High Temperature Superconductor Bearings, Appl. Phys. Lett., 59, (9), pp. 1132-1134, 1991.

B. R. Weinberger and L. Lynds (United Technologies Research Ctr.), J. VanVelzeh, H. Eaton, J. R. Hull, T. M. Mulcahy, and S. A. Basinger, Characterization of Composite High-Temperature Superconductors for Magnetic Bearings, IEEE Trans. Magn., 27, pp. 2415-2421 (1991).

J. L. Wu (Westinghouse Science and Technology Ctr.), J. T. Dederer (WSTC), P. W. Eckels (WSTC), S. K. Singh (WSTC), J. R. Hull, R. B. Poeppel, C. A. Youngdahl, J. P. Singh, M. T. Lanagan, and U. Balachandran, Design and Testing of a High-Temperature Superconducting Current Lead, 1990 Applied Superconductivity, Snowmass Village, CO, Sept. 24-28, 1990, Proc. published in IEEE Trans. Magn., 27(2), 1861-1865 (1991), also published in Electr. Manuf., 19-23 (May 1991).

Patent

J. M. McKee, Hydrogen Gas Sensor and Method of Manufacture. U.S. Patent No. 5,012,672, awarded May 7, 1991.

Analytical Thermal-Hydraulics

Section Manager: W. T. Sha

Staff: M. Bottoni, F. C. Chang, T. H. Chien, J. Ding, H. M. Domanus,

K. Sakai, R. C. Schmitt, J. G. Sun, X. Q. Wang

Secretary: S. A. Moll

The main research disciplines of the Analytical Thermal-Hydraulics Section are heat transfer; single-phase and multiphase fluid flow; and mathematical, phenomenological, and numerical modeling. The Section's research activities are divided into four major areas: (a) code development, physical modeling, and numerical simulations for reactor applications; (b) thermal analysis of the APS storage ring; (c) generic casting modeling; and (d) fossil energy applications and modeling.

Code Development, Physical Modeling, and Numerical Simulations for Reactor Applications

Code Development

Since 1976, the Section has been engaged in developing three-dimensional, steady/transient, single-phase/multiphase computer codes for predicting temperature, velocity, pressure, and phasic concentration distributions in reactor component and multiple-component systems under normal and off-normal operating conditions. The developed codes fall into two series, COMMIX and BODYFIT (see tables on next page). The two series have a wide range of applications and complement one another. The COMMIX series has been developed for global thermal-hydraulic analysis of large complex systems, whereas the BODYFIT series—which uses boundary-fitted coordinate transformation—has been developed for examination of small specific regions and analysis of detailed local thermal-hydraulic phenomena in such regions. Development of the BODYFIT code has halted due to funding limitations.

COMMIX

The codes in the COMMIX series allow global analyses of heat transfer and fluid flow phenomena in a single component (such as a rod bundle, reactor plenum, piping system, or heat exchanger) or in a multicomponent system, i.e., a combination of these components. A unique feature of the COMMIX code is its use of a new porous-media formulation in which volume porosity, directional surface porosity, distributed resistance, and distributed heat sources or sinks are employed to analyze continuum/quasicontinuum flow domains. The concept of directional surface porosity is new; it greatly facilitates modeling of velocity and temperature fields in anisotropic media, and in general it improves resolution and accuracy. The full three-dimensional, transient, conservation equations of mass, momentum, and energy are solved as a boundary-value problem in space and as an initial-value problem in

Table 1. *COMMIX Series*

COMMIX-1	Single Phase
COMMIX-1A	" "
COMMIX-1B	" "
COMMIX-1C	" "
COMMIX-1D	Single Phase/Multicomponents (ongoing work for ALWR containment analysis)
COMMIX-PPC	Condenser Single Phase/Multicomponent (completed code development, but need validation with pertinent experimental data)
COMMIX-M	Single Phase/Multiphase (under development)

Table 2. *BODYFIT Series*

BODYFIT-1FE	Single Phase
BODYFIT-2FE	Single Phase/Two Phase
BODYFIT-2PE	Single Phase/Two Phase

time. The COMMIX codes have been developed and refined over several years, and a large number of computations for complex situations already have been performed to validate the general features and wide range of applications. The status of three COMMIX codes, namely, COMMIX-1C, COMMIX-1D, and COMMIX-PPC, is described below.

COMMIX-1C

COMMIX-1C is the latest COMMIX series of single-phase codes and represents a number of improvements over the previous versions of single-phase COMMIX codes. Specifically, these improvements are (a) a new finite-volume formulation for the mass, momentum, and energy equations to extend the applications to subsonic compressible flows and to make the calculations more robust; (b) a flow-modulated skew-upwind discretization scheme to reduce numerical diffusion; (c) two new matrix solvers for the discretized equations to increase the flexibility and efficiency of numerical computation; and (d) a k - ϵ two-equation turbulence model that is more robust and better validated than those in previous COMMIX codes. Documentation of the COMMIX-1C code was completed in September 1990 and released through the NRC's Office of Nuclear Regulatory Research.

COMMIX-1D

The following list describes the important additions and improvements that will be implemented into COMMIX-1C to form a new code called COMMIX-1D.

- *Multicomponent Model.* Implemented into COMMIX-1D and capable of predicting concentration distribution of air, steam, and hydrogen in a reactor component such as the containment vessel.
- *Condensation and Evaporation Models.* Applicable for AP-600 Passive Containment Cooling System (PCCS) and implemented into COMMIX-1D. These models are being validated with integral and 1/8-scale experimental data for the Westinghouse AP-600 PCCS reactor.
- *Liquid-Film Tracking Model.* For AP-600 PCCS; has been developed and implemented into COMMIX-1D and computes liquid-film thickness, velocity, and temperature on inside and outside walls of steel containment vessel. The liquid film formed outside the containment steel vessel wall is due to flooding water at the top of the dome of the containment steel vessel, and the liquid film formed inside the vessel wall is due to filmwise condensation.
- *Radiation Model.* Will be developed and implemented into COMMIX-1D; this model is needed to account for radiation heat transfer from the steel containment vessel to the air baffle in the AP-600 PCCS.
- *Six-Equation Anisotropic Turbulence Model.* Some concern has been expressed about the potential inadequacy of the k - ϵ two-equation isotropic turbulence model for buoyancy-driven flows. This model was programmed in the COMMIX-1C code and has been applied to buoyancy-driven flows. To improve the capability of the COMMIX code, a six-equation anisotropic turbulence model has been developed and implemented into the COMMIX code. The six-equation anisotropic turbulence model consists of the k , ϵ , ϕ^2 , $\phi u'$, $\phi v'$, and $\phi w'$ transport equation, where ϕ is the temperature fluctuation, and u' , v' , and w' are fluctuating velocity components. This model has now been incorporated into the COMMIX code as a user option. Limited assessment and validation of the model have been conducted.
- *Second-Order Differencing (QUICK-Type) with Oscillation Dumping Scheme.* Any multidimensional finite-difference calculations of fluid flow and heat transfer will introduce numerical diffusion. To reduce this, two new second-order differencing with oscillation dumping schemes have been developed and will be implemented in the COMMIX-1D code as user options: QUICK (Quadratic Upstream Interpolation for Convective Kinematics) with FRAM (Filtering Remedy and Methodology), and LECUSSO (Local Exact Consistent Upwind Scheme of Second Order) with FRAM. These new schemes are better than the existing first-order Flow Modulated Skew Upwind Differencing (FMSUD) scheme in the COMMIX-1C code. It should be noted that the FMSUD scheme was implemented in the energy equation only in the COMMIX-1C code; the new schemes have been implemented in the mass,

momentum, and energy equations. Experience to date shows that LECUSSO is generally more stable than QUICK. A report on the subject is under preparation. Limited validations have been carried out and the results are very promising.

- *Three-Dimensional Conduction Model.* To predict flow stratification accurately in a piping system, a three-dimensional conduction model for the pipe wall is needed. The existing one-dimensional conduction model for the pipe wall in the COMMIX-1C code has been modified and extended to three dimensions. The new model has been implemented in the COMMIX-1D code as a user's option. Results have been compared with an analytical solution and are in good agreement.

Condenser Code (COMMIX-PPC)

Condenser performance can significantly influence the overall performance of an entire power plant. The typical power plant condenser is a shell-and-tube heat exchanger. Steam enters the condenser from the turbine exhaust, mixes with leaked air flowing through the tube bundle, and exits to the hot well. The steam is condensed to the liquid state by releasing the latent heat of vaporization, which is transferred to the cooling water through the condenser tubes. As the steam-and-air mixture moves toward the heat transfer surface, the noncondensable gases accumulate on the tube surfaces. These gases can significantly increase the thermal resistance between the steam and cooling water, thus reducing the steam condensation rate. To improve the heat transfer rate, the noncondensable gases must be reduced and removed.

Although noncondensable gases have a significant effect on condenser performance, heat transfer also depends on tube material, tube wall thickness, local steam pressure, stream velocity, cooling water velocity, and effects of inundation and biofouling. To improve and optimize the design and performance of power plant condensers, we are developing a new computer code (COMMIX-PPC) based on the incomplete in-house version of the COMMIX-M computer code. The COMMIX-PPC is a three-dimensional, time-dependent, multicomponent (multispecies) shell-and-tube-condenser computer code with the following features: shell- and tube-side heat transfer coupling; computing of both shell-side and tube-side velocity, temperature, and pressure distributions of steam and cooling water and air concentration distribution on the shell side; and accounting for effects of inundation, vapor shear, and biofouling. This work is sponsored by the Taiwan Power Company, and the code development work has been completed and is in the validation phase. However, no pertinent experimental data are available to validate the condenser computer code.

Physical Modeling and Numerical Simulations

A current research focus is improvement of the physical modeling and convergence rate of numerical simulations of natural circulation, flow stratification, and mixing processes.

Natural Circulation

It is recognized that natural circulation has a significant impact on the course of an accident and its consequences. The NRC has identified natural circulation as one of the most important processes that can mitigate and possibly prevent a reactor accident, and thus this phenomenon is a major area of uncertainty in reactor safety analysis. The conceptual designs for the next generation of LWRs expand the use of passive features from emergency core-cooling functions to decay-heat removal. These passive cooling features rely mainly on natural circulation and are designed to prevent damage to the core or containment after a design-basis accident such as a loss-of-coolant accident or a main steam-line break accident without operator action.

Flow Stratification

Flow stratification, normally in association with a large temperature difference, occurs in various PWR and BWR components during normal and off-normal operating conditions. Thus, when flow stratification occurs in a reactor component, it will be subject to an additional thermal stress from the local temperature difference. Several nuclear power plants have reported failure of reactor components due to flow stratification. Not only can it cause reactor shutdown due to an unisolatable leak resulting from failure of a reactor component, but it also has significant implications to reactor safety and can alter both the sequence and consequence of a reactor accident. Therefore, the causes of flow stratification must be understood; more important, we should be able to predict when and where flow stratification will occur, as well as the magnitude of temperature difference associated with the phenomenon.

Mixing Processes

Two mixing problems are encountered in reactor design and safety analyses. One is the mixing of hot and cold fluids, and the other is mixing of fluids with high and low or no concentration of certain species. Problems in this area include boron dilution and hydrogen mixing. These two mixing problems can occur simultaneously.

Thermal Analysis of Advanced Photon Source Storage Ring

Two thermal hydraulic analyses have been carried out for APS; some design changes were made at least partly on the basis of COMMIX calculational results.

- A thermal-hydraulic analysis of the APS storage ring has been completed, with the objective to calculate the air temperature and velocity distributions in the ring and the temperature distribution in the girder under several design configurations. The numerical model consists of the solid structures in the ring (cooling-air duct, girder, magnets, and power units) and the heat sources generated from the power units and the magnets. The results showed that with the power units located under the girder plate, the

temperature distribution in the girder will be considerably nonuniform. The analysis has made a major contribution to the APS decision to move the power source outside the storage ring.

- An analysis for temperature distributions in the girder under various heating mechanisms has been performed. The objective was to evaluate techniques for maintaining uniform temperature distributions in the top and bottom plates of the girder. To perform this analysis, a three-dimensional heat conduction model was implemented in the COMMIX code; it considered the heat conduction from the magnets to the girder and the heat convection from the solid surfaces to the surrounding air. The effects of using water ducts attached to the girder plates were also examined. Calculational results showed that temperature difference between the top and bottom girder plates will be minimal when the water ducts are used.

Generic Casting Modeling

Fluid Flow and Heat Transfer Phenomena in the Casting Process

Casting is one of the most direct methods of producing industrial parts or components in desired shapes. Although the casting process has been in existence for thousands of years, it involves a host of complex phenomena that are still not thoroughly understood. The principal phenomena are fluid flow and heat transfer, because they control grain size and shape, porosity, and segregation of alloying elements in the final cast product. The flows in casting molds typically have both free surfaces and moving solidification boundaries. Air and other gases may be trapped within the molten material, forming a two-component mixture. Nonuniform heat transfer, coupled with large temperature gradients and buoyancy forces, produces natural convection currents in the molten metal. In certain circumstances, the flow may exhibit turbulence.

Casting Modeling is a research and development program involving a consortium that originally comprised ANL, Caterpillar, and Teledyne Corporation and began in March 1990. Early in 1992, Teledyne Corporation withdrew from the consortium for financial reasons. This caused a disruption, but the program has been restarted and most of the original objectives remain intact.

The overall program objective is to develop state-of-the-art software for simulating the casting process; this is of immediate use to members of the casting industry. Expected benefits include superior castings produced with significantly reduced capital and operating costs. In this regard, each percentage-point reduction in the defect rate of the nation's casting production would achieve an annual energy saving of \$38 million. Furthermore, the program will benefit new product development, when first-run rejects are excessive and often cost-prohibitive. The importance of this program is further confirmed by industry's participation, which provides a 50% cost share for Phase I over a three-year period ending in 1993.

The program draws upon the experience obtained while developing computer programs at ANL for the analysis of nuclear reactor systems under the Analytical Thermal-Hydraulic Research Program. New extensions are being developed to simulate the phenomena of mold filling and solidification. Transient free- and fixed-surface thermal hydraulics is a unique feature of this software. The interface for this model will be provided by existing software packages that are compatible with hardware currently in use or affordable by industry. Phase I of this project will produce a software package for distribution by the American Foundrymen's Society. Subsequently, the program will continue—without government participation—to work on proprietary problems of industry.

A critical aspect of the program is the development of a user-friendly interface to be used in constructing the simulation and interpreting the results. The PATRAN software package has been installed on the project's engineering workstation; this represents the first use of this industry-standard software package at ANL. PATRAN is used to construct the geometry of the mold and to view the simulation results. An automatic mesh generator has been developed to approximate a PATRAN geometry suitable for simulation. Software has been developed to translate simulation results to a form that can be viewed with PATRAN. Development of a mold-fill model and a solidification model is being completed

*Casting image obtained with PATRAN software,
showing simulated filling of a wheel mold*

in the simulation module. The figure below shows the simulated filling of a wheel mold. At the time shown, the advancing free surface of the metal is solidifying and is forming a cold shot. Software is being developed in the UNIX operating system to handle the flow of information between the various modules of the Casting Processing Simulator (CAPS) package.

Fossil Energy Applications and Modeling

In the past year, we have worked on two new initiatives in the fossil energy area. One is the development of a new initiative on Suspension Advanced Research Objective (SARO). The other is in-house research to understand the mechanisms for depletion of solids near a solid wall for solid/liquid flow in a pipe. Numerical analyses of such flow will be carried out and the calculational results will be compared with experimental data obtained via NMR and provided to us by the Lovelace Medical Foundation.

Recent Work by the Analytical Thermal-Hydraulics Section

Publications

M. Bottoni and F. C. Chang, Development and Verification of an Anisotropic Turbulence Model in the COMMIX-1C/ATM Computer Code, presented at 5th Intl. Topical Mtg. on Nuclear Reactor Thermal Hydraulics (NURETH-5), Salt Lake City, Sept. 21-24, 1992.

M. Bottoni, T. H. Chien, H. M. Domanus, W. T. Sha, and Y. Shen, Implementation of the Flow-Modulated Skew-Upwind Difference Scheme in the Commix-1C Code - A First Assessment, Presented at XIV Mtg. of the Liquid Metal Boiling Working Group (LMBWG), ENEA Brasimone, April 16-18, 1991.

F. C. Chang, M. Bottoni, and W. T. Sha, Development and Validation of the k-c Two-Equation Turbulence Model and the Anisotropic Turbulence Model in the COMMIX Code, ANL/ANTHRP-44 (Jan. 1992).

F. C. Chang, M. Bottoni, and W. T. Sha, Contribution of the Benchmark Computation for Turbulent Natural Convection in a Square Cavity with the Computer Code Commix-1C, presented at EUROTHERM-ERCOFTAC Workshop, Delft, The Netherlands, Mar. 25-27, 1992.

J. Ding, R. W. Lyczkowski, W. T. Sha, A. Altobelli (Lovelace Medical Foundation), and E. Fukushima (Lovelace Medical Foundation), Analysis of Liquid-Solids Suspension Velocities and Concentrations Obtained by NMR Imaging, presented at NSF/DOE Workshop on Flow of Particles and Fluids, Gaithersburg, MD, Sept. 17-18, 1992.

Jianmin Ding, T. H. Chien, and W. T. Sha, COMMIX Computations for the HDR Containment Steam Blowdown Experiment ISP-23, ANL/ATHRP-46 (June 1992).

K. Sakai, M. Bottoni, and W. T. Sha, Benchmark Computation for Turbulent Natural Convection in a Square Cavity Using the Computer Program COMMIX-1C/QUICK with the High-Order Numerical Scheme Quick, Submitted to EUROTHERM-ERCOFTAC Workshop, Delft, The Netherlands, Mar. 25-27, 1992.

S. H. Sheen, W. P. Lawrence, H. T. Chien, and A. C. Raptis, Ultrasonic Flow Imaging System -- A Feasibility Study, ANL/FE-91/3 (1991).

Y. Shen, M. Bottoni, and W. T. Sha, Implementation of the Flow-Modulated Skew-Upwind Difference Scheme in the Momentum Equation of the COMMIX-1C Program: a First Assessment, Submitted to Multiphase Flow Research Institute, ANL, ANL/MFRI-8 (Feb. 1991).

J. G. Sun and W. T. Sha, Implementation of Three-Dimensional Heat Conduction Models for Solid Structures in COMMIX-1C Program, ANL/ATHRP-45 (May 1992).

J. G. Sun and W. T. Sha, B. Kaufer, G. Lanik, J. Rosenthal, and N. Su, USNRC, Analysis of Thermal Stratification, presented at 1991 Winter Mtg., Amer. Nucl. Soc., Nov. 10-14, 1991, San Francisco.

J. G. Sun, Y. H. Shen, and W. T. Sha, Analysis of Flow Stratification in the Surge Line of the Comanche Peak Reactor, NUREG/CR-5456, ANL-91/6 (1991).

Thermal and Mechanical Sciences

Section Manager: M. W. Wambsganss

Principal Investigators: S. S. Chen, S. U. Choi, J. A. Jendrzejczyk,
K. E. Kasza

Support Staff/Visiting Scientists: Y. Cai, S. H. Chen, D. M. France,¹
N. T. Obot,¹ S. Zhu

Technicians: R. K. Smith, A. Wantroba

Secretary: J. A. Stephens

Students: B. Knodel,² P. Rosas-Velez,³ T. N. Tran²

Staff backgrounds and program activities in the Thermal and Mechanical Sciences Section represent many diverse areas, including structural dynamics, thermal-hydraulics, heat transfer, fluid flow, and vibrations. Staff expertise and experience is primarily in experimentation and testing, but also extends to modeling. A particular strength of the Section is the array of test facilities that it operates. These include the Flow-Induced Vibration Test Facility (an 8,000-gpm water flow loop), the Flow and Heat Transfer Test Facility (a computer-controlled, thermal-hydraulic, transient, nonisothermal, 2,200-gpm water loop), a low-velocity water channel, an ice-slurry test facility, an adiabatic two-phase flow apparatus, a small-channel heat transfer test apparatus, and a 500-gpm water loop; under construction is a high-temperature and high-heat-flux interfacial heat transfer test apparatus.

The Section performs applied research and component development and performance testing, and it also provides consultation. Current activities include research in the areas of flow-induced vibration, multiphase flow and heat transfer in small channels, ice slurries for district cooling, contact heat transfer for a fusion reactor design, and vehicle/guideway interaction dynamics for high-speed trains using magnetic levitation. Activities in support of the Advanced Photon Source (APS) project at ANL include ongoing vibration studies and microchannel cooling of the optical elements in the beamline. Consulting is being carried out for the Taiwan Power Company (Taipower).

Flow-Induced Vibrations

Flow-induced vibrations of heat exchanger and steam generator tube arrays continues to be an area of interest and concern for the process and utility industries. The Thermal and Mechanical Sciences Section conducts three programs in this area: (a) a DOE Office of Basic Energy Sciences (BES) sponsored program to develop and apply methods to identify and characterize nonlinear and chaotic vibrations in fluidelastic systems, (b) an ANL Laboratory Directed Research and Development (LDRD) program to measure fluid force

¹Special Term Appointee.

²University of Illinois at Chicago.

³University of Puerto Rico.

coefficients in tube bundles subjected to crossflow, and (c) a multiyear program funded by Taipower to develop methods for predicting tube vibration in heat exchangers.

Clearances between tubes and support-plate holes are inherent in the design of heat exchangers and steam generators. The existence of the clearances gives rise to a nonlinear system. The potential for chaotic motion associated with fluidelastic instability of nonlinearly supported tubes in crossflow was demonstrated by the Section with its development of an unsteady-flow theory that uses a set of force coefficients available from the literature and a bilinear mathematical model. Effective tools, including phase plane portraits, power spectral density representations, Poincaré maps, Lyapunov exponents, fractal dimensions, and bifurcation diagrams, were used to distinguish periodic and chaotic motions when the tubes vibrate in the instability region. The results show periodic and chaotic motions in the region corresponding to fluid-damping controlled instability. The nonlinear supports, with symmetric or asymmetric gaps, were shown to significantly affect the distribution of periodic, quasiperiodic, and chaotic motions in the instability region of the tube-support-plate-inactive mode. Experiments are being performed with a row of tubes in crossflow to demonstrate the phenomenon and to obtain data that can be compared with theoretical results.

Prediction of the flow-rate/velocity thresholds for fluidelastic instability of tube arrays in crossflow for various designs requires a complete set of motion-dependent fluid forces, including inertia, damping, and stiffness. At present, it is not possible to predict these forces from the fundamental principles of fluid dynamics and the theory of elasticity, and as a consequence, it is necessary to measure these forces. Toward this end, an experiment was designed with a row of tubes in crossflow, in which the center tube is force-excited and the motion-dependent fluid forces acting on it and on adjacent tubes are measured with strain-gauge technology. A low-velocity water channel has been refurbished, a measurement technique refined and calibrations performed, a data acquisition program written, and experiments initiated.

The flow-induced vibration program funded by Taipower includes consultation on current flow-induced vibration problems/concerns; training of Taipower staff through seminars, short courses, and staff visits; experimental studies of fluidelastic instability in tube arrays; assistance in development of computer codes; and development of a design guide.

Multiphase Flow and Heat Transfer

Compact heat exchangers have numerous attributes, including high thermal effectiveness, large heat transfer surface-to-volume ratio, small size, low weight, and design flexibility. To facilitate the design and optimization of compact heat exchangers for use in energy conversion and utilization systems, we are performing fundamental studies of multiphase flow and heat transfer in flow channels representative of compact heat exchangers, under the sponsorship of the DOE Office of Energy Conservation, Advanced Industrial Processes Division. This research is focused on the flow boiling of refrigerants in small, typically noncircular channels, with the objective of developing design correlations and predictive methods.

We have conducted adiabatic experiments with air/water mixtures in horizontal, rectangular channels of different sizes and orientations; developed flow pattern maps; and evaluated and improved pressure-drop correlations. A small-channel heat transfer test apparatus was designed and fabricated. Flow boiling tests of refrigerant R-113 in a small-diameter circular tube have been completed. The resulting data were used to evaluate state-of-the-art heat transfer correlations. Interpretation of the data led us to conclude that the nucleation mechanism dominates as a result of inherently high boiling numbers in small channels and the extension of the slug flow pattern to relatively high mass qualities. Current experiments are focused on flow boiling of R-12 in a small rectangular channel measuring 4.04 x 1.70 mm.

A cooperative research and development agreement (CRADA) was negotiated with Modine Manufacturing Company of Racine, WI. The DOE Office of Energy Research is funding ANL, and Modine is cost-sharing with in-kind contributions. The agreement integrates the expertise developed at ANL in studying two-phase flow and heat transfer in small passages with the heat exchanger design and commercialization experience of Modine. The objectives are to (a) identify the flow-passage size and geometry that yield the highest-performance heat transfer surface for condensation, (b) develop validated correlations for condensation and two-phase pressure drop, (c) apply these correlations in the optimal design of heat transfer surfaces for condensers used in vehicular applications, and (d) performance-test a prototype condenser. The experiment design and the design and fabrication of a small-channel condensation heat transfer test apparatus have been initiated.

Ice Slurries for District Cooling

We have proposed to the DOE Utility Systems Division a four-year field testing program for district cooling with ice slurries, with joint sponsorship provided by Northern States Power (NSP) and the Electric Power Research Institute (EPRI). The three proposed sponsors have agreed to the program, which was initiated in FY 1992. Ice/water slurries have the potential for significant energy savings and cost reduction in district cooling systems. As a result of pumping a higher-energy-density fluid, the piping, a major cost item in a district cooling system, can be made much smaller. There are also potential savings associated with the heat exchangers because they can also be smaller and can be made to operate more efficiently. The initial phase of the program will provide cooling to the NSP utility service center, and the second phase will extend service to satellite loads in a U.S. post office and a medical center. ANL's role is to provide project management for DOE, in addition to conducting development testing and participating in data analysis and interpretation. The system has undergone detailed design. ITT's Fluid Handling System Division is donating major equipment and is collaborating in the design of a control system for the ice-slurry cooling systems. Testing will begin in the second quarter of FY 1993.

Supplementing the field testing program, ANL is engaged in a program of fundamental studies of ice slurries, which are being performed in a joint effort with the University of Illinois at Chicago. The objective of this research is to develop design correlations for heat transfer and pressure drop with ice-slurry flows. Such correlations will ultimately be required in the application of the technology and in the design of optimized systems; the correlations would be functions of such parameters as ice-crystal size and ice volume

fraction. While some work on pressure drop has been performed, heat transfer—which is important both during slurry transport and its use in heat exchangers—has yet to be addressed in detail in the engineering literature. The program was initiated in FY 1991. An ice-slurry test apparatus, which uses a direct-freeze ice generator, was designed and fabricated and preliminary experiments have been performed.

Advanced Photon Source

The Advanced Photon Source (APS), currently under construction at ANL, is a user facility for synchrotron radiation research. In the facility, positrons circulate in a storage ring $\approx 1,040$ ft in diameter and emit photons (X-rays) of high intensity. Successful operation of the APS requires a very stable positron closed orbit. A contributor to beam instability is vibration of the storage ring quadrupole magnets. Such vibration can lead to distortion of the positron closed orbit and to potentially unacceptable beam emittance growth. The vibration criteria are very stringent (on the order of $0.1 \mu\text{m}$ at frequencies greater than ≈ 15 Hz). With the objective of ensuring that vibrations will not degrade the performance of the machine, Section staff have been involved in an ongoing program of vibration studies that support APS design and development.

In the vibration study program, we have measured (a) ground motion and structural foundation response at the APS site and (b) vibration characteristics and response of the storage-ring magnet support assemblies. Measurements at the site are performed during both noisy periods (construction in progress) and quiet periods. The results provide useful insights relative to expected vibration levels; foundation response to ambient ground motion during quiet periods was found to be generally well within the established vibration criteria. Each storage-ring magnet support assembly consists of a girder mounted on an alignment jack. Two different support assembly designs, one featuring jackscrews for alignment and the other wedge-type alignment jacks, were evaluated by their measured dynamic characteristics (natural frequencies, modes, damping and transfer functions), and the wedge-type jacks were recommended. Plans are being made to establish a test bed for the magnet support assemblies within MCT.

A new activity, initiated in FY 1992, involves the development and implementation of an APS site vibration-monitoring system. This system will include a network of ground/foundation/equipment vibration monitors installed at the facility, as well as a method for quickly detecting unacceptable vibration levels and identifying the associated vibration source(s). A source-detection scheme based on triangulation was devised, evaluated, and shown to be a potentially useful tool. However, successful implementation will require knowledge of the dynamic characteristics of the buildings and large mechanical systems at the site, as well as the duty cycles of operating equipment. In another study, a pile driver served as an excitation source for determination of the attenuation characteristics of surface waves at the site. The attenuation is the result of both geometric and material damping. A coefficient of attenuation was derived to account for the site-specific material damping. The dynamic characteristics of APS buildings and equipment are being measured and cataloged as they come on line.

The first optical elements of the APS beamlines absorb a tremendous amount of energy that is rapidly transformed to heat as they reflect the beam. Cooling these high-heat-load

X-ray optical elements is a formidable task. Conventional cooling technologies are not adequate, and a new and innovative cooling method is needed. Requirements include minimizing thermal distortion, vibration, and temperature gradients. The Section is engaged in an ANL Laboratory Directed Research and Development (LDRD) program to evaluate microchannel cooling and the effect of header design on flow-induced vibrations. Design has been completed for a microchannel heat exchanger that uses liquid nitrogen as the cooling fluid. Vibration of existing gallium-cooled optical element designs has also been measured, with the objective of evaluating the effect of coolant flow rate on vibration.

Maglev Studies

High-speed vehicles that employ magnetic levitation (maglev) have received worldwide attention. The National Maglev Initiative (NMI) was established in May 1990 to assess the potential of maglev in the United States and ANL is supporting the NMI program. The guideway of a maglev line is expected to cost about 60-80% of the initial capital investment for a maglev system, and Section staff are contributing to the maglev program at ANL with an emphasis on the guideway. The technical approach involves (a) establishment of baseline information on state-of-the-art technologies relative to guideways, vehicles, magnet field, and flow field; (b) collection of engineering data in these areas; (c) identification of research needs; and (d) recommendation of technical approaches for obtaining the necessary data and developing computer codes and design guides.

One of the tasks of the NMI is to determine the status of existing computer software. We are providing existing computer codes used for solving maglev problems involving mechanical forces and dynamics that can be applied to the design of maglev vehicles and guideways. Available computer codes are presented, and their capabilities, modeling techniques, extent of verification and validation, and related information are provided.

Dynamic interactions between the maglev vehicle and guideway are being studied, with an emphasis on the effects of vehicle and guideway parameters. Two dynamic models for the vehicle were developed. In one model, the vehicle is considered a moving force traveling at various speeds on a simply supported single- or two-span beam. In the second model, the vehicle is considered one-dimensional, with two degrees of freedom; the primary and secondary suspensions of the vehicle are represented with lumped masses, linear springs, and dampings. The Bernoulli-Euler beam equation is used to model the characteristics of a flexible guideway, and guideway synthesis is based on a modal analysis method. Analyses have been performed to understand response characteristics under various loading conditions, and to provide benchmark data for verification of existing comprehensive computer programs and some basic guidelines for maglev system design.

For safety, maglev systems must be stable. Magnetic forces are basically position-dependent; some forces are also velocity-dependent. These motion-dependent magnetic forces can induce various types of instability. In addition, the periodic structure of the motion-dependent forces may also induce parametric resonance and combination resonance. We conducted a study, based on scoping calculations and simple mathematical models, to consider the stability of maglev systems.

ITER Heat Transfer Experiments

Interfacial heat transfer characteristics, as well as macroscale and microscale thermomechanical interactions between layers, are being studied in support of the International Thermonuclear Experimental Reactor (ITER) engineering design effort. Section staff have designed a facility to test multilayered-slab models of fusion blanket designs. The facility will allow testing under prototypical high heat fluxes, high temperatures, thermal gradients, and variable mechanical loadings in a helium gas environment. Global one-dimensional heat transfer across blanket specimen layers sandwiched between hot and cold plates will be achieved. The engineering design of the test apparatus has shown that it is important to use multidimensional thermomechanical analysis of sandwich-type composites to adequately analyze heat transfer; this will also be true for the engineering design of the ITER.

Consulting

Consulting efforts are valuable because they provide Section staff with early indications of real-life problems and concerns faced by utilities and industry. Additionally, consulting provides an opportunity to apply the expertise developed in the course of conducting fundamental and applied research.

At present, the Section provides consultation to Taipower on flow-induced vibrations and related areas. Completed efforts included the presentation of seminars and short courses at Taipower, and evaluation of flow-induced vibration of heat exchangers and large control valves.

Recent Work by the Thermal and Mechanical Sciences Section

Publications

Y. Cai, S. S. Chen, and D. M. Rote (Center for Transportation Research), Vehicle/Guideway Interaction in Maglev Systems, ANL-92/19 (1992).

Y. Cai, S. S. Chen, D. M. Rote, and H. T. Coffey, Vehicle/Guideway Interaction for High Speed Vehicles on Flexible Guideway, presented at CSME Forum 1992 "Transport 1992+," June 1-5, 1992, Montreal.

Y. Cai and S. S. Chen, Chaotic Vibrations of Tubes with Nonlinear Supports in Crossflow, to be presented at 1992 ASME/JSME/IMEchE/CSME/IAHR Int. Symp. on Flow-Induced Vibration and Noise, Nov. 8-13, 1992, Anaheim, CA.

Y. Cai and S. S. Chen, Chaotic Vibrations of Nonlinearly Supported Tubes in Crossflow, ANL-92/18 (1992).

Y. Cai, S. S. Chen, and T. M. Mulcahy, Fluidelastic Instability of Loosely Supported Tubes, presented at 9th Symp. on Energy Engineering Sciences, Argonne National Laboratory, May 13-15, 1991.

Y. Cai, S. S. Chen, and S. Chandra (Northeast Utilities Service Co.), A Theory for Fluidelastic Instability of Tube-Support-Plate-Inactive Modes, ASME Pressure Vessels and Piping Conf., San Diego, June 23-27, 1991, J. of Pressure Vessel Tech., Vol. 114, No. 2, May 1992, pp. 139-148.

Y. S. Cha, J. R. Hull, and U. S. Choi, Cryostabilization of High Temperature Superconducting Magnets Using Subcooled Flow in Microchannels, presented at 1992 Applied Superconductivity Conf., Chicago, Aug. 23-28, 1992.

Y. S. Cha, John R. Hull, Thomas M. Mulcahy, and Thomas D. Rossing (Northern Illinois U.), Effect of Size and Geometry on Levitation Force Measurements Between Permanent Magnets and High-Temperature Superconductors, submitted to 5th Joint MMM-Intermag Conf., Pittsburgh, June 18-21, 1991; J. Appl. Phys., Vol. 70, No. 10, Pt. II, pp. 6504-6506, Nov. 1991.

S. S. Chen and Y. Cai, Wind Induced Vibration of a Stack, to be presented at 1992 ASME Winter Annual Mtg., Anaheim, CA, Nov. 8-13, 1992.

S. S. Chen and D. M. Rote, A Review of Vehicle/Guideway Interaction of Maglev Systems, presented at ASME Pressure Vessels and Piping Conf., June 21-25, 1992, New Orleans.

S. S. Chen, Flow-Induced Vibrations in Two-Phase Flow, Transactions of ASME, Vol. 113, May 1991, pp. 234-241 (reprinted from J. of Pressure Vessel Tech.).

J. M. Chenoweth (Heat Transfer Research, Inc.) and M. W. Wambsganss, DOE/ANL/HTRI Heat Exchanger Tube Vibration Data Bank (Addendum 8), ANL-CT-80-3 Addendum 8.

S. U. Choi and T. N. Tran, Performance of a Shell-and-Tube Heat Exchanger with Friction-Reducing Surfactant Solutions, presented 82nd Annual Conf. on Intl. District Heating and Cooling Assn., San Francisco, June 22-26, 1991.

U. S. Choi and T. N. Tran (Purdue U.-Calumet), Experimental Studies of the Effects of Non-Newtonian Surfactant Solutions on the Performance of a Shell-and-Tube Heat Exchanger, presented at ASME Winter Annual Mtg., Atlanta, Dec. 4-6, 1991.

J. A. Jendrzejczyk, M. W. Wambsganss, and R. K. Smith, Vibration Response of the Linac Floor Slab to Ambient Ground Motion, APS Internal Note APS/IN/VIB/92-1 (1991).

J. A. Jendrzejczyk, M. W. Wambsganss, and R. K. Smith, Vibration Study of the APS Storage Ring Girder/Support Assembly with Wedge-Type Alignment Jacks, ANL/APS/IN/VIB-92/2 (1992).

J. A. Jendrzejczyk, M. W. Wambsganss, and R. K. Smith, Evaluation of a Vibration Source Detection Scheme, ANL/APS/IN/VIB-92/3 (1992).

J. A. Jendrzejczyk and M. W. Wambsganss, Vibration Considerations in Support of the Design of the Advanced Photon Source at Argonne National Laboratory, presented at Conf. on Vibration Control in Microelectronics, Optics, and Metrology, 1991 Symp. on Optical Sci. and Eng., Nov. 3-8, 1991, San Jose, CA.

K. E. Kasza, ANL ITER High-Heat-Flux Blanket-Module Heat Transfer Experiments, ANL/FPP/TM-262 (1992).

K. E. Kasza, J. Hietala (Northern States Power), R. D. Wendland (EPRI), and F. Collins (U.S. DOE), Ice Slurry Cooling: Development and Field Testing, presented at 83rd Annual Conf. of Intl. District Heating and Cooling Assn., Boston, June 14-17, 1992.

L. Papp (Research Institute of Vitkovice, Czechoslovakia) and S. S. Chen, Turbulence Induced Vibration of Tube Arrays in Two-Phase Flow, submitted to J. of Pressure Vessel Tech.

M. W. Wambsganss, J. A. Jendrzejczyk and D. M. France (U. of Illinois at Chicago), Determination and Characteristics of the Transition to Two-Phase Slug Flow in Small Channels, to be presented at 1992 ASME Winter Annual Mtg., Anaheim, CA, Nov. 8-13, 1992.

M. W. Wambsganss, D. M. France (U. of Illinois at Chicago), J. A. Jendrzejczyk, and T. N. Tran, Boiling Heat Transfer in a Horizontal Small-Diameter Tube, submitted to ASME J. of Heat Transfer.

M. W. Wambsganss, J. A. Jendrzejczyk, and D. M. France, Two-Phase Flow and Pressure Drop in Flow Passages of Compact Heat Exchangers, 1992 SAE Intl. Congress and Exposition, Detroit, Feb. 24-28, 1992, SAE Technical Paper Series 920550.

M. W. Wambsganss, J. A. Jendrzejczyk, D. M. France (U. of Illinois at Chicago), and N. T. Obot (Clarkson U.), Frictional Pressure Gradients in Two-Phase Flow in a Small, Rectangular Channel, *Experimental Thermal and Fluid Sci.* 1992; 5:40-56, Elsevier Sci. Publ. Co., Inc., New York, pp. 40-56.

Ji Wang, Free Vibrations of Stepped Circular Plates on Elastic Foundations, submitted to *J. Sound Vib.* as Letter to Editor.

Instrumentation and Nondestructive Evaluation

Section Manager: A. C. Raptis

Principal Investigators: S. L. Dieckman, W. A. Ellingson, N. Gopalsami,

D. S. Kupperman, S. H. Sheen,

Support Staff: J. P. Bobis,¹ W. E. Brewer, H. T. Chien, G. A. Forster, N. Gopalan,

T. Hentea, D. A. Holloway, E. R. Koehl, W. P. Lawrence, R. Popper,

K. J. Reimann, A. Saigal, E. A. Sivers¹

Technicians: R. N. Lanham

Secretary: N. M. Heeg

Students: A. M. Beckman, G. Bostrom, M. P. Brada, S. Ellsworth, T. Gardiner,

T. P. James, J. Kestel, J. Krueger, W. O'Connell, G. Phillips, G. Ramos

Visiting Foreign Scientist: J. R. Ling²

Visiting Industrial Scientist: G. Happoldt³

The Instrumentation and Nondestructive Evaluation Section conducts research and development in a broad range of energy-related technologies. Major areas of responsibility are the development of instruments and NDE techniques for fossil energy, conservation, and nuclear technologies. Another strong area for the Section has been the development of sensors and technologies for arms control and treaty verification. We have been actively involved in a number of ANL or national initiatives such as the Mission to Mars, Global Warming, and Competitiveness of American Industry. The projects described below give a clear indication of the breadth of our work.

Arms Control

Millimeter-Wave Detector

This program is funded by the DOE Office of Arms Control and Nonproliferation. The goal is to develop a millimeter-wave sensor for remote detection of chemicals associated with chemical weapons production. The sensor is based on millimeter-wave multispectral radiometry and will measure rotational emission signatures of key molecules released from the exhaust and vent stacks of a chemical weapons production plant.

Included in a feasibility study that we conducted were (a) selection of appropriate molecules, (b) radiometric modeling of emission temperatures of molecular clouds of known density added to the atmosphere, (c) modeling of plume transport and dispersion in the atmosphere, (d) analysis of background effects, and (e) expected detection sensitivity

¹Special Term Appointee.

²People's Republic of China.

³Caterpillar Inc.

and selectivity. Based on the feasibility results, two millimeter-wave systems were designed and built: an active millimeter-wave spectrometer in the 75-110 GHz range, and a passive millimeter-wave radiometer/spectrometer in the 77.3-93.3 GHz range.

Using the active spectrometer, we studied the spectral characteristics of some simulant gases, as well as the effect of pressure on spectral peaks and widths. The results will establish candidate molecules that are suitable for the passive-mode testing. The passive system will be tested for its detection capability first in the laboratory and then in the field. Based on these results, multichannel systems will be built covering the 75-110 GHz and 210-300 GHz frequency windows, in which the atmosphere is nearly transparent to millimeter waves. The sensor will ultimately be tested in a fly-by mode looking down on the plume.

Photothermal Techniques

This program is funded by the DOE Office of Arms Control and Nonproliferation under the Advanced Concepts Project. The use of photothermal techniques is investigated for treaty verification. The specific objectives are to (a) nondestructively detect tampering of tags and seals placed on treaty-limited items and (b) screen a stockpile of declared warheads for nonconformance. In photothermal techniques, pulsed heat (e.g., by means of a flash lamp) is applied to one surface of the part under test and an infrared video camera is used to map the surface-temperature changes as the part cools. Because the heat-flow pattern is affected by thermal property changes in the material, subsurface defects such as disbonds manifest themselves through changes in local surface temperature. These techniques are noncontacting and nondestructive and can provide quick inspection of the treaty-limited items.

A photothermal imaging system was built with flash lamps, a state-of-the-art infrared camera, a personal computer with plug-in boards for real-time image capture and storage, and pulse sequence and timing electronics for data acquisition. Using this system, we tested materials that are representative of the case materials of treaty-limited items, such as Kevlar and graphite-epoxy composites. With appropriate signal processing, fabricated undercuts 1 to 2 mm deep from the front surface were readily detected. Future work will involve a systematic assessment of detection capability for deep subsurface defects.

Ultrasonic Intrinsic Tag Evaluation

The DOE Office of Arms Control and Nonproliferation is funding this program at ANL to conduct an independent adversary study on the ultrasonic intrinsic tag, which uses subsurface ultrasonic images as the unique signatures of the scanned surface. The study includes evaluation of the tag concept and the performance of the tag inspection system. Two prototype inspection systems, developed by Battelle Pacific Northwest Laboratory, have been evaluated for their performance. Problems and concerns have been identified, including those in both software and hardware. The vulnerability of the tag concept has also been examined. A portion of this work is classified.

Ultrasonic Weight Sensor

A portable lightweight weighing station is needed to monitor moving vehicles at an arms-controlled site for treaty verification. ANL is funded through an advanced-concept project to develop a portable weight sensor based on ultrasonic methods. A sensor consisting of layers of PVDF films, which are piezoelectric, has been fabricated and tested. The sensor responds to dynamic loads; thus it is sensitive to vehicle speed. Output signals are analyzed for their frequency content, peak amplitude, and time of flight between loads.

Smart-Material Seal

This is a new program funded under the ANL advanced-concept project for arms control and treaty verification. The program will develop a "smart seal" that not only can provide a means for authentication but also contains a memory to record its history. The proposed seal will be a strip of metal with embedded sensors such as PVDF films. Whenever the seal is attacked, the sensors produce responses that are recorded with the time of occurrence. Different seal geometries will be examined; each has its specific application.

Tamper-Revealing Ceramic-Cable Seals

A novel, closed-loop security seal that uses a cable made from flexible silicon carbide fibers was designed and fabricated for an arms control program. Ultrasonic waves are launched in the fibers by a magnetostrictive transducer and propagate through the ceramic-fiber cable. Distortions of the propagating wave lead to a unique ultrasonic fingerprint of the cable that is detected by the transmitting transducer operating in a pulse-echo mode. The ultrasonic fingerprint is digitized and stored for future reference. Tampering is revealed as a change in the ultrasonic fingerprint. The seal was successfully tested, and authentication procedures were developed and demonstrated. This relatively inexpensive, chemically resistant, and easily implemented seal has application to treaty verification and arms control and could be used to seal storage facilities, containers, valves, or military devices.

Fossil Energy

Ultrasonic Flow Imaging System

The objective of this program, which is funded by the DOE Fossil Energy AR&TD program, is to develop an ultrasonic flow imaging system for mixed-phase flows. The system will use arrays of transducers that are nonintrusive to the flow. The transducers will be sequentially pulsed to generate ultrasonic pulses that propagate through the flow. The attenuated and scattered ultrasonic signals will be detected by the same transducers around the sensing volume. Flow images will be reconstructed from the detected signals on the basis of theoretical models describing attenuation and scattering. To increase spatial

resolution, a multistep time-of-flight wedge has been designed and evaluated. The wedge can split a transducer pulse into many pulses that are clearly separated in the time domain. The wedge can reduce the number of transducers required in the transducer array design.

Ultrasonic Nondestructive Evaluation

We have developed an alternative acousto-ultrasonic (AU) technique for nondestructive evaluation of fiber-reinforced composites. The technique measures the time of flight of AU waves, instead of the stress wave factor, by low-frequency (0.5-MHz) transducers and relates them to material properties and fiber orientation. AU waves propagate in composites with two distinct velocities that correspond to propagations in the fiber and in the composite matrix. Thus, the AU technique can also be applied to evaluation of the interfacial strength between fibers and matrix and to detections of defects and debonding of fiber-reinforced composites.

Development of Nondestructive Characterization for Monolithic Solid Oxide Fuel Cells

The development of a monolithic solid-oxide fuel cell (MSOFC) continues as a joint project between ANL and Allied-Signal Aerospace Corporation's Los Angeles Division. Funding is provided by DOE/Fossil Energy through the Morgantown Energy Technology Center. To ensure reliability of the final product and reliable process control, a survey was conducted to assess which nondestructive characterization methods might be developed for each step in the process. The ceramic process under development is hot-rolled calendering used to manufacture the thin (0.01 to <0.015 in.) individual layers or trilayers. Of primary concern are uniformity of chemical composition and density in these ceramic layers that are to be used in this electrochemical fuel cell.

Development of Nondestructive Characterization for Continuous-Fiber Ceramic Matrix Composites

Fracture toughness of ceramics can be improved significantly with the use of newly developed continuous-fiber ceramic matrix composites (CFCC). However, the reliability of mechanical properties depends on many factors, including fiber/matrix interfacial shear strength, type of chemical bond at the fiber/matrix interface, density uniformity, direction of the fibers, and type of fiber and whether multifiber tows or single large individual filaments (>50 μm in diameter) are used.

In cooperation with Oak Ridge National Laboratory, which also is funded by DOE/Fossil Energy, CFCCs made of SiC/SiC are being produced by chemical vapor infiltration (CVI). SiC two-dimensional weave structures are being laid up in 0/30/60, 0/45, and 0/90° cloth orientations with changes in the CVI process. At ANL, we are developing nondestructive characterization methods to measure various characteristics of these materials. Specifically, we are developing 3-D microfocus X-ray computed tomographic (MXCT) imaging methods to detect and measure (a) axial and radial density variation and (b) fiber orientation by coupling image processing with X-ray image data. In this case, the 3-D

MXCT system has been totally designed and built in-house at ANL. Data acquisition and control are via an IBM 386/33 MHz PC, and image reconstruction is done with a SUN SPARC II/GS 24-bit-plane workstation. Image analysis and display are done either on the SUN workstation or a Macintosh IIfx high-resolution display system. The results so far have shown that fiber orientation can be determined to $\pm 5^\circ$ with image data that are 256 x 256 and with our current 8-bit detector limit. The MXCT system is being modified with a detection system to allow 14-bit detection with 1024 x 1024 display that will significantly improve resolution and detection sensitivity. Extensive software modifications have also been made.

This year, we also began to address the issue of interfacial shear-strength measurement, studying acoustic wave propagation characteristics as a function of known interfacial shear strength. Oak Ridge produced a set of SiC/SiC CVI specimens with 0/30/60 layup and different carbon-coating thickness. Thickness variations affect interfacial shear strength. By using acousto-ultrasonic methods with signal processing, we measured differences in interfacial bond strength. This work will continue next year.

To begin to understand the effects of fiber/matrix-bond chemical interactions, we began using NMR spectroscopy to study fiber-surface chemistry; ^{29}Si , ^{13}C , and ^{17}O were studied. Magic angle spinning (MAS) was employed in several magnetic-field-strength NMR systems at ANL to study these effects. No correlations have yet been established relative to interfacial shear strength.

Conservation

Development of Nondestructive Characterization for Whisker-Based and Monolithic Ceramics

Part 1: Monolithic Si_3N_4

Several near-term advanced heat engine components will likely be made of advanced monolithic structural ceramics. Because these materials are very susceptible to fracture by flaws, the detection of flaws and high reliability in ceramic production is imperative. In a joint activity with the Norton Advanced Ceramic Company, funded by the DOE Assistant Secretary for Conservation and Renewable Energy/Heat-Engine Materials Program, we are playing an integral role in helping to improve Si_3N_4 ceramic processing reliability by NDC. We are engaged in two NDC methods this year: (a) X-ray computed tomography for mapping density distributions in slip-cast and injection-molded specimens and (b) nuclear magnetic spectroscopy for characterizing colloidal suspensions used in slip-casting and in powder preparation for injection molding.

We have demonstrated to Norton that radial and axial density variations exist throughout process-development tensile specimens. The radial density variations demonstrated to Norton how a change in mold design had affected density distribution. Nuclear magnetic resonance (NMR) spectroscopy has been shown to be capable of detecting distributions of surfactants, deflocculants, and sintering aids that heretofore

could not be measured; moreover, these data, when correlated with other rheological data (viscosity, pH), can be used to improve casting.

Part 2: Whisker-Based (SiC(w)/Si₃N₄)

In another joint research activity with industry, this time with Garrett Ceramic Components (GCC) of Allied-Signal Aerospace Corporation, we are developing NDC methods that can be used to detect differences in density (axial and radial) in pressure-slip-cast SiC(w)/Si₃N₄. Two methods are being studied: 3-D X-ray microfocus computed tomography (MXCT) and NMR computed tomography (NMRCT). Partially sintered specimens with different whisker loadings (20, 23, 27 and 30 wt.% ratios) are used to examine these processing parameters. In this effort, GCC produces the specimens, ANL develops the NDC methods and acquires NDC data, and GCC subsequently measures the density destructively. Destructive data are then compared directly to the nondestructively obtained data. The MXCT data have shown excellent agreement with destructively obtained data on specimens with different L/D ratios and at all whisker loadings. NMRCT is a less-well-developed method and has not so far been able to provide high-quality images. Another NMRCT problem is the fluid used to fill the pore space: it is a known carcinogen. Recent emphasis on environment, health, and safety (ES&H) has caused us to drop this aspect of this research.

In FY 93, working in conjunction with Dr. O. O. Omatete of the Materials and Ceramics Division at Oak Ridge National Laboratory, we will evaluate the use of NMR in the process development and on-line production of gel-cast composites. Nondestructive NMR imaging and spectroscopic studies will enable visualization of the polymerization process, calculation of polymerization rates, and measurement of viscosity within the component. Additionally, imaging methods will be employed for flaw determination and these results will be correlated with those obtained through destructive analysis and fracture mechanics.

Part 3: Digital Radiography

In cooperation with the Garrett Auxiliary Power Division of Allied-Signal Aerospace Corporation, we are assessing the potential of digital image processing to enhance the detection capabilities of ordinary X-ray films. Several sets of X-ray films were taken of Si₃N₄ specimens with known flaw populations of various types and sizes. We are digitizing these films by various methods, concentrating on full-field CCD cameras with back-lighted films. Once digitized, the data are then manipulated in the computer by various image-processing methods, e.g., low-pass, high-pass filtering, 3 x 3 or 5 x 5 Laplacian filters, etc. At present, no analytical method seems available to systematically select the sequence of image-processing steps to best enhance the features of interest. We have worked on both 8- and 14-bit digitization.

Development of Nondestructive Characterization for Continuous-Fiber Ceramic Matrix Composites

A new 10-year program was begun this year in the Doe Office of Industrial Technology (OIT) to address process-reliability issues relative to production and eventual industrial

application of CFCCs. As part of this large program, development of nondestructive characterization methods are identified as a necessary and critical technology. Argonne (specifically, MCT) was identified as the technical lead in this task. The total CFCC program involves 10 industrial teams consisting of CFCC producers, independent test facilities, and end users. A separate task is identified for development of support technologies. The project involves both oxide-based (Al_2O_3 , ZrO_2) materials and nonoxide (SiC , Si_3N_4) materials.

The first task for ANL this year is to produce a topical report that clearly identifies the primary characteristics to be measured and to determine which nondestructive characterization methods can likely be used to measure these characteristics. Because of past research activities and results, initial experimental work will likely emphasize 3-D MCXT, time-resolved-infrared imaging, acousto-ultrasonics, and NMR. Future work will probably involve neutron diffraction.

Superconductivity Pilot Center

Development of X-Ray Imaging for High-Temperature Ceramic Superconductor Process Control

Variations in initial processing, nonuniform extrusions, nonuniformities from cold isostatic pressing (CIP), etc., of superconductor materials can likely result in axial and radial density variations that cause defects during sintering. In the case of extrusion methods, high-density inner "cores" seem to develop when the extrusion is not optimal. Further, it seems that some "preferred texture" results from this process. Being studied is the ability of high-resolution X-ray imaging methods to detect these process-induced variations in YBCO materials doped with Ag.

In the case of CIPed material, cracking seems to develop after the CIPing process. We are trying to establish the detectable level of cracking and whether it is related to some density variation induced by the process.

High-Temperature Superconductivity

NDE of High-Temperature Ceramic Superconductors

Under a joint program between ANL and Allied Signal, ultrasonic and neutron diffraction techniques have been applied to the evaluation of high-temperature ceramic superconductors. Applications for these superconductors include magnetic bearings (yttrium barium copper oxide [YBCO]) and wire (bismuth strontium calcium copper oxide [BSCCO]). The objective of the work with YBCO is to develop a method to characterize texture which is an important factor in the levitating force. A rapid, room-temperature ultrasonic scan of YBCO components can provide information about the texture and integrity of the material. Neutron diffraction has been used to validate the ultrasonic technique for the determination of texture. Strong correlations have been found between texture and

levitating force, and experiments have shown that the longitudinal velocity of sound can be used easily to characterize texture and thus levitating properties. Velocity maps (courtesy of NASA) have been generated to show the variations in velocity of sound on a millimeter scale. These maps can be used to characterize the spatial variations in levitating force of YBCO samples in a rapid manner at room temperature.

Low-frequency (140 kHz) ultrasonic velocity of sound measurements have been used to monitor the fabrication (powder-in-tube process) of silver-clad BSCCO superconducting ribbons. The measurement of sound velocity is used to indicate the presence of a liquid phase during sintering. Knowledge about the presence of the liquid phase is very important for optimizing the fabrication process in order to generate the highest critical currents possible. Ultrasonic waves are launched by a magnetostrictive transducer (140 kHz), propagate down an Inconel rod, and then enter the ribbon. Pulse-echo techniques are used to determine the variations in sound velocity at temperatures up to 850°C. An analysis of preliminary results indicates that this ultrasonic technique can be used to monitor the processing of this type of ceramic superconductor.

Work For Others

State of Illinois Grant: Infrared Imaging Development for Thick Thermal Barrier Coatings

The development of high-efficiency diesel engines with acceptable exhaust emissions requires a ceramic coating on components in the combustion zone. Plasma-sprayed ZrO₂ coatings are being developed by Caterpillar Inc. This project, cofunded by the State of Illinois and Caterpillar, is developing time-resolved-infrared imaging (TRIR) methods to detect coating adhesion.

In this joint project, Caterpillar is producing specimens of different coating thicknesses (up to 3.5 mm), with and without known disbond regions, on different substrates. Argonne has developed a TRIR laboratory that includes a state-of-art infrared camera coupled to a personal computer, specially developed software, and several systems to apply known-input heat pulses. Software developed at ANL is used to study differences in thermal transients, which are then used to detect regions of nonbonding. In addition, ANL is using an analytical heat-transfer model SINDA to predict sensitivity levels. The models are being run in the new SUN SPARC II/GS workstation. These analytical models have been shown to correlate very well with experiment data. Destructive analysis completed by Caterpillar has provided necessary input data on flaw thicknesses. Also Caterpillar has made necessary thermal property measurements on each component in the layered structure for the input to the model.

The results of this project were successful enough that Caterpillar has entirely duplicated the ANL infrared laboratory and will make necessary modifications to put the test facility into the process-development measurement stream.

DARPA: Development of NDC Methods for Ceramic Bearings

Ceramic bearings, both hybrid (metal races and ceramic rolling elements) and all-ceramic cannot be reliably used in industry today because no method exists to nondestructively characterize the individual components. Further, no model is satisfactory as a lifetime predictor from tribological test methods. As part of a three-year effort by DARPA to apply ceramic bearings, ANL has the lead role in developing nondestructive characterization methods. These NDC methods will be used to acquire data that will be coupled to analytical predictive models, as well as to experimental correlations. The overall program involves ceramic-rolling-element producers, rolling-element finishing companies, universities, and both military and industrial end users.

At present, two NDC methods are being developed at ANL: (a) laser scattering methods for measuring surface and near-surface characteristics and (b) high-resolution 3-D microfocus X-ray computed tomography (MXCT) for detecting internal defects.

To address surface characterization and near-surface measurements, we established a laser scattering laboratory that uses an He-Ne laser (35 mW), together with many optical components for both laser beam insertion and subsequent detection of the scattered light. A CCD array camera is coupled to an IBM 486/33 MHz computer to handle data acquisition, image processing and image display. This is coupled to the SUN SPARC II/GS for additional signal analysis. A granite table floating on a special vibration-isolation system is used to support the optical system work station. A special software package was developed in-house to allow correlation of detected signals. By using optical Fourier transform displays and correlation-type signal processing, we have demonstrated a detection sensitivity on as-machined surfaces of 0.1 to 3.17 μm . What is very important is the ability of the laser-scattering method to detect "lay," or direction of machining, as well as subsurface defects.

The 3-D MXCT system, used in other projects described earlier, has been significantly modified for this project. First, a new 14-bit CCD array camera detection system has been added to provide the necessary dynamic range and spatial resolution. A new water-cooled X-ray target was added to provide output stability at higher anode currents. The primary ceramic bearing material under study is hot-pressed Si_3N_4 .

ANL/BIO-Imaging Research Technology Exchange on X-Ray Computed Tomography

This is a new project funded through the DOE/ANL Technology Transfer Center. The purpose of this project is to couple the expertise at ANL/MCT and Bio-Imaging Research Inc. (BIR) in the area of computer algorithm development for high-resolution microfocus X-ray computed tomography. Specifically, to improve the spatial resolution of local regions in an object to be studied, a region-of-interest algorithm is being developed to allow only a portion of an object to be reconstructed in the computer. This also allows a large object (one normally too large for the X-ray system) to be studied by X-ray CT. The algorithm has now been developed, installed at ANL and BIR, debugged, and tested. Results to date show improved detection sensitivity, especially on large objects.

ANL/Caterpillar Technology Exchange on Infrared Imaging and X-Ray Computed Tomography

This is a Cooperative Research and Development Agreement (CRADA) funded through the DOE/ANL Technology Transfer Center. The purpose is to couple the expertise at ANL and Caterpillar in the area of nondestructive characterization of thick thermal barrier coatings. This builds on the State of Illinois Technology Challenge Grant (see thick thermal barrier coatings). In this effort, both X-ray imaging, to study individual ceramic materials for engine applications, and infrared imaging for thick thermal barrier applications are being studied. In the X-ray work, Si_3N_4 , SiC , and ZrO_2 are being studied by microfocus X-ray computed tomographic imaging for defect detection sensitivity. In the infrared imaging work, emphasis is on pre- and postengine exposure to assess the effects of combustion gases on infrared detection sensitivity to disbands between the graded ceramic composition layers.

Acid Rain Effects on Marble and Limestone

The effects of acid rain and weathering on marble and limestone are being studied in a continuous 10-year exposure program. Annual and multiyear field-exposed samples from several instrumented test sites in the eastern United States are analyzed yearly. Compositional changes are evaluated by chemical means, material losses by gravimetry and laser-moiré interferometry, and discolorization by tri-stimulus color measurements. Chemical results for exposure periods up to eight years indicate a predominant increase in sulfate concentration on the groundward surface proportional to H^+ concentration and, to a degree, to exposure period. Nitrate, chlorine, and fluorine formation on the groundward surfaces is orders of magnitude below that of sulfate. The rain-rinsed skyward surfaces remain unchanged in their composition during the same exposure period. Preexposed samples obtained from demolished buildings, which initially showed a high sulfate concentration, lost some of the sulfate on skyward surfaces during exposure. Gravimetry and laser-moiré interferometry indicate a linear relationship between material losses, rain amount, and exposure time. Tri-stimulus color measurement confirms the noticeable yellowing of marble and darkening of limestone, especially at groundward surfaces of exposed samples. Studies to assess the significance of the different phenomena and establish a quantitative correlation are continuing.

NMR Imaging of Polymeric Materials

This program was funded by Dow Chemical Company, and the goal is to develop advanced solid-state NMR imaging techniques for mapping chemical and physical properties in polymers and polymeric blends. Imaging techniques were developed to produce two- and 3-D images of rigid materials and will facilitate the nondestructive analysis of chemical properties such as extent of polymerization, molecular mobility, and solvent diffusion rates. Under this program, the first proton (^1H) 3-D NMR imaging of a rigid polymer was acquired (see figure on next page).

Optical photograph (top left) and two orientations of a surface-reconstructed 3-D proton (^1H) NMR image of a rigid polymer specimen

ANL/BIR Technology Exchange on Solid-State NMR Imaging

This program is funded as a CRADA through the DOE/ANL Office of Technology Transfer. It combines the expertise of both MCT and that of Bio-Imaging Research Inc. in designing advanced RF coils, cavity structures, and associated electronics. The goal is to design highly homogeneous RF structures to be used in concert with solid-state NMR imaging technology developed at ANL. Work in this program is proceeding with the computer modeling of resonant structures and the simulation of appropriate RF tuning methods. This program will promote further advances in the field of imaging with application in advanced ceramics, biomedicine, and polymeric technology.

Application of Neutron Diffraction to Determination of Strain in Engineering Materials

Neutron diffraction experiments to measure residual strains were carried on metal-matrix composites provided by General Electric. Residual strains in the constituents of several composites (candidate materials for advanced aircraft engines) were measured at room temperature and as a function of temperature to help establish the effect of fiber material and processing on the performance of these composites. The results were also used to validate computer models developed to predict mechanical properties. Similar

work on advanced composites was carried out for NASA and Dow Corning. The ANL Intense Pulsed Neutron Source and General Purpose Powder Diffractometer were employed for these studies.

Acoustic Leak Detection and Location for District Heating and Cooling Systems

A program is underway to develop an in-stream acoustic microphone for leak detection and location in underground steam pipes. This project is a collaborative effort between DOE, Consolidated Edison of New York, and NRG Thermal (a subsidiary of Northern States Power). Two types of acoustic sensors have been evaluated at ANL with a laboratory-scale steam system. Results indicate that the microphones can withstand the elevated temperature and pressures of a steam system and can be inserted into live pipes by "hot tapping." Cross-correlation analysis of acoustic signals is used to locate leaks. Having the sensors placed directly in the steam significantly improves the chances of accurately locating leaks in buried pipes. Further testing in the field will involve Consolidated Edison and/or Northern States Power steam systems.

Ultrasonic Viscometer

An in-process, real-time, and nonintrusive viscometer is needed for many industrial processes dealing with non-Newtonian fluids. One such process, identified by the Industrial Technology Institute (ITI), is the plastic injection mold, in which the viscosity of molten plastics inside the extruder is important. Currently, plastic viscosity is estimated from the temperature, a direct-measurement instrument is not available. ITI has therefore funded ANL to develop an ultrasonic viscometer based on the acoustic impedance measurement. Different sensing wedges have been tested for their sensitivity and accuracy in measuring fluid viscosity.

Recent Work by the Instrumentation and NDE Section

Publications

H. T. Chien, S. H. Sheen, and A. C. Raptis, An Acousto-Ultrasonic NDE Technique for Monitoring Material Anisotropy, presented at 19th Annual Review of Progress in Quantitative Nondestructive Evaluation, San Diego, July 19-24, 1992.

H. T. Chien, S. H. Sheen, and A. C. Raptis, An Alternative Approach of Acousto-Ultrasonic Technique for Monitoring Material Anisotropy of Fiber-Reinforced Composites, to be published in IEEE Transactions on Ultrasonics, Ferroelectrics, and Frequency Control.

C. Y. Chu, J. L. Routbort, N. Chen, A. C. Biondo, D. S. Kupperman, and K. C. Goretti, Mechanical Properties and Texture of Dense Polycrystalline $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_x$, Superconductor Sci. and Tech. 5, 306-312 (1992).

S. L. Dieckman, P. Rizo, N. Gopalsami, J. P. Heeschen (Dow Chemical Co.), and R. E. Botto (CHM), Three-Dimensional Microscopic ^1H NMR Imaging of Rigid Polymers, Reprint from J. of Amer. Chem. Soc., 1992, 114, pp. 2717-2719.

Stephen L. Dieckman, Three-Dimensional NMR Imaging of Polymers and Polymer Blends, presented at 33rd Rocky Mountain Conf. on Analytical Chemistry, Denver, July 28-Aug. 2, 1991.

S. L. Dieckman, P. Rizo (LETI, France), N. Gopalsami, and R. E. Botto (CHM), Three-Dimensional Nuclear Magnetic Resonance and X-Ray Microtomographic Imaging of Composite Materials, Proc. of Material Research Soc. Mtg., Boston, Fall, 1990.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. L. Dieckman, D. Singh, E. A. Sivers, and S. H. Sheen, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, to be published in Proc. 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1992.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. L. Dieckman, D. Singh, E. A. Sivers, and S. H. Sheen, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, to be published in Proc. 6th Ann. Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1992.

W. A. Ellingson, D. L. Holloway, J. Ling (Chinese Academy of Sciences), E. A. Sivers, J. P. Pollinger (Garrett Ceramics Components Div., Allied Signal Aerospace Co.), and H. C. Yeh (Garrett), Nondestructive Evaluation Development for Process Control, to be published in Ceram. Tech. Sec. of Proc. 1991 U.S. DOE Automotive Tech. Develop. Contractors' Coordination Mtg. (CCM), Oct. 28-31, 1991, Dearborn, MI. Proceedings to be published by Soc. of Automotive Engineers.

W. A. Ellingson, J. P. Singh, D. L. Holloway, S. H. Sheen, D. Singh, E. A. Sivers, and S. L. Dieckman, Development of Nondestructive Evaluation Methods and Prediction of Effects of Flaws on the Fracture Behavior of Structural Ceramics, presented at 6th Annual Conf. on Fossil Energy Materials, Oak Ridge, TN, May 14-16, 1992.

W. A. Ellingson and T. Luethi (EMPA Laboratory, Zurich, Switzerland), X-ray Computed Tomographic Imaging, Ceramic Technology for Advanced Heat Engines Project: Semiannual Progress Report for Oct. 1990 through Mar. 1991, ORNL/TM-11859, pp. 450-457.

W. A. Ellingson, N. Gopalsami, S. L. Dieckman, and T. Luethi (EMPA Laboratory, Zurich, Switzerland), Development of Nondestructive Characterization Technologies for Process Control of Ceramics, to be published in Proc. Iktetani Conf., 5th Intl. Symp. on Nondestructive Characterization of Materials, Karuizawa, Japan, May 27-June 3, 1991.

W. A. Ellingson, D. L. Holloway, J. T. Pollinger ((Garrett Ceramics Components Div., Allied Signal Aerospace Co.), and H. Yeh (Garrett), Analysis of Pressure Slip-cast SiC/w/Si₃N₄ by X-ray Computed Tomography, presented at 6th Annual Conf. on Composites and Advanced Ceramics, Cocoa Beach, FL, Jan. 7-10, 1992.

W. A. Ellingson, R. A. Lowden (ORNL), and D. L. Holloway, Characterization of Continuous Fiber SiC/SiC CVI Composites by X-ray Microtomography, presented at 16th Annual Conf. on Composites and Advanced Ceramics, Cocoa Beach, FL, Jan. 7-10, 1992.

W. A. Ellingson, Editor Vol. 217, Advanced Tomographic Imaging Methods for the Analysis of Materials, Materials Research Soc., Pittsburgh.

W. A. Ellingson, J. P. Singh, N. Gopalsami, S. L. Dieckman, A. S. Wagh, C. -Y. Chu, and T. Luethi, Development of Nondestructive Evaluation Methods of Effects of Flaws on the Fracture Behavior of Structural Ceramics, Proc. 5th Annual Conf. on Fossil Energy Materials, May Conf., Oak Ridge, TN, May 13-16, 1991, CONF-9105184, ORNL/FMP-91/1, pp. 137-153.

W. A. Ellingson, M. W. Vannier (Mallinckrodt Institute of Radiology/Washington U.), and D. P. Stinton (Oak Ridge National Laboratory), Application of X-Ray Computed Tomography to Ceramic/Ceramic Composites, Proc. Characterization of Advanced Materials Symp., 20th Ann. Mtg. of Intl. Metallographic Soc., Monterey, CA, July 27-28, 1987, Plenum Press, New York, eds. W. Altergott and E. Henneke, pp. 9-25.

W. E. Ellingson, N. Gopalsami, S. L. Dieckman, and T. Luethi (EMPA Laboratory, Zurich, Switzerland), Development of Nondestructive Evaluation Technologies for Process Controls of Ceramics, presented at Iketani Conf., 5th Intl. Symp. on Nondestructive Characterization of Materials, Japan, May 27-June 3, 1991.

N. Gopalsami, P. Rizo (LETI, France), and W. A. Ellingson, Detection Sensitivity of X-Ray CT Imaging for NDE of Green-State Ceramics, to be published in Proc. 18th Annual Review of Progress in Quantitative NDE, sponsored by Iowa St. U./Ames Lab., and Bowdoin College, Brunswick, ME.

D. S. Kupperman, Neutron Diffraction NDE, INVITED PAPER to be published in Nondestructive Testing Handbook on Advanced NDT Techniques by Amer. Soc. for Nondestructive Testing.

D. S. Kupperman, A. C. Raptis, and R. L. Lanham, Detection and Location of Leaks in District Heating Steam Systems: Survey and Review of Current Technology and Practices, ANL-92/5 (1992).

D. S. Kupperman, S. Majumdar, J. S. Gregar (CD), J. P. Singh, S. Dorris, N. Gopalsami, S. Dieckman, A. C. Raptis, R. A. Valentin, and T. K. Hunt (ERIM), Materials Research for Sodium Engine Development, to be published in Proc. 26th Intersociety Energy Conversion Engineering Conf., Boston, Aug. 4-9, 1991.

D. S. Kupperman, S. Dorris, S. H. Sheen, R. Palm (RAS), J. Dusek, and A. C. Raptis, Assessment of Tamperproof Ceramic Seals, ANL/ACTV-90/5 (1990).

D. S. Kupperman, S. Majumdar, and J. P. Singh, The Application of Neutron Diffraction Time-of-Flight Measurements to the Study of Strain in Composites, to be published in Proc. NATO Advanced Research Workshop on Measurement of Residual Stress and Applied Stress Using Neutron Diffraction, Oxford, UK, March 18-22, 1991.

D. S. Kupperman, S. Majumdar, J. P. Singh, and A. Saigal, The Application of Neutron Diffraction Time-of-Flight Measurements to the Study of Strain in Composites, INVITED PAPER to be presented at NATO Advanced Research Workshop on "Measurement of Residual Stress & Applied Stress Using Neutron Diffraction," Oxford, UK, March 18-22, 1991.

D. S. Kupperman, S. Majumdar, and J. P. Singh, Application of Neutron Diffraction to the Determination of Residual Strain in Advanced Composites, INVITED PAPER submitted to J. of Neutron News.

D. S. Kupperman, J. P. Singh, and S. Majumdar, Use of Neutron Diffraction in the Measurement of Residual Strains in Composites, presented at Ann. Spring Mtg. of Am. Ceram. Soc., Cincinnati, April 1991.

D. S. Kupperman, J. P. Singh, and R. L. Hitterman, Use of Neutron Diffraction to Determine Grain-Size Effects on Strain in $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$, submitted to J. Appl. Phys.

S. Majumdar, J. P. Singh, D. S. Kupperman, and A. D. Krawitz (U. of Missouri, Columbia), Application of Neutron Diffraction to Measure Residual Strains in Various Engineering Composite Materials, J. Eng. Mater. and Tech., Jan. 1991, Vol. 113, pp. 51-59.

R. B. Poeppel, K. C. Gorretta, U. Balachandran, I. Bloom, S. E. Dorris, J. T. Dusek, J. E. Emerson, K. E. Gray (MSD), M. Hash (CTD), S. A. Johnson (CTD), R. T. Kampwirth (MSD), M. Kullberg, D. S. Kupperman, M. T. Lanagan, V. A. Maroni (CTD), R. L. McDaniel, J. H. Meiser (CTD), J. J. Picciolo, J. P. Singh, and C. A. Youngdahl, Practical Superconductor Development for Electrical Power Applications - Annual Report for FY 1990, ANL-90/47 (1990).

R. B. Poeppel, K. C. Goretta, U. Balachandran, I. Bloom, Y. S. Cha, S. E. Dorris, J. T. Dusek, J. E. Emerson, K. E. Gray, M. C. Hash, J. R. Hull, J. S. Kallend, R. T. Kampwirth, M. A. Kirk, D. S. Kupperman, M. T. Lanagan, V. A. Maroni, R. L. McDaniel, D. J. Miller, J. J. Picciolo, J. L. Routbort, J. P. Singh, and C. A. Youngdahl, Practical Superconductor Development for Electrical Power Applications - Annual Report for FY 1991, ANL-91/28 (1991).

A. C. Raptis, W. A. Ellingson, R. E. Botto, H. Yeh, and J. P. Pollinger (Garrett Ceramic Components Div., Allied-Signal Aerospace Corp.), Nuclear Magnetic Resonance Imaging, Ceramic Technology for Advanced Heat Engines Project: Semiannual Progress Report. for Oct. 1990 through Mar. 1991, ORNL/TM-18859, pp. 458-460.

A. Saigal (Tufts U.) and D. S. Kupperman, Residual Thermal Strains and Stresses in Nickel Aluminide Matrix Composites, Scripta Metallurgica et Materialia, Vol. 25, published by Pergamon Press, Inc., pp. 2547-2552 (1991).

A. Saigal, D. S. Kupperman, and S. Majumdar, Residual Strains in Titanium Matrix, High Temperature Composites, J. Mater. Sci. and Eng., A150 (1992), pp. 59-66.

A. Saigal and D. S. Kupperman, Application of Neutron Diffraction to Measure Residual Strains in High Temperature Composites, presented at and for publication in proceedings of 6th Japan-U.S. Conf. on Composite Materials, Orlando, FL, June 22-25, 1991.

S. H. Sheen and A. C. Raptis, Advanced Research in Instrumentation and Diagnostics Technology, presented at Advanced Res. and Tech. Development (AR&TD) Gasification and Gas Stream Cleanup Systems Contractors' Review Mtg., Sept. 15-17, 1992, Morgantown, WV.

S. H. Sheen, W. P. Lawrence, H. T. Chien, and A. C. Raptis, Ultrasonic Flow Imaging System -- A Feasibility Study, ANL/FE-91/3 (1991).

J. P. Singh, D. S. Kupperman, S. Majumdar, S. E. Dorris, N. Gopalsami, S. L. Dieckman, R. A. Jaross, D. L. Johnson, J. S. Gregar, R. B. Poeppel, A. C. Raptis, and R. A. Valentin, Sodium Heat Engine Development Program: Phase I Final Report, ANL-91/45 (1992).

J. P. Singh, D. S. Kupperman, and S. Majumdar, Strengthening of Composites by Internal Stresses: Determination by Neutron Diffraction, INVITED PAPER presented at 1st Intl. Symp. on the Science of Engineering Ceramics, Koda, Japan, Oct. 21-23, 1991.

J. P. Singh, D. S. Kupperman, and S. Majumdar, Role of Internal Stresses in Improvement of Mechanical Properties of Ceramic Composites, INVITED PAPER presented at 44th Pacific Coast Regional Mtg. of Amer. Ceram. Soc., San Diego, Oct. 31-Nov. 2, 1991.

J. P. Singh, R. A. Guttischo, D. S. Kupperman, J. T. Dusek, and R. B. Poeppel, Strength/Grain-Size Relationships and Internal Stresses in $\text{YBa}_2\text{Cu}_3\text{O}_x$ Superconductors, for publication in Proc. 3rd Symp. on High-Temperature Superconductors: Processing and Microstructure Property Relationships, 1991 TMS Mtg. and Exhib. New Orleans, Feb. 17-21, 1991.

E. A. Sivers, D. L. Holloway, W. A. Ellingson, and J. Ling (Chinese Academy of Science), Development and Application of Local 3-D X-ray Reconstruction Software for Imaging Critical Regions in Large Ceramic Turbine Rotors, presented at 19th Annual Review for Progress in Quantitative Nondestructive Evaluation, San Diego, July 19-24, 1992.

Transportation of Hazardous Materials

Section Manager: G. F. Popper

Principal Investigators: R. D. Carlson, R. R. Fabian, J. J. Oras, E. M. Pennington,

F. G. Prohammer, D. T. Raske, V. L. Shah, P. Turula

Secretary: J. L. Fisher

The Transportation of Hazardous Materials Section primarily provides direct technical assistance to DOE in reviewing Safety Analysis Reports for Packaging (SARPs) of nuclear shipping packages for compliance with DOE Orders and with NRC and Department of Transportation regulations. In addition, the Section provides technical support to DOE on a variety of generic waste management and transportation issues, including the production and distribution of training and public information videos.

SARP Review Group

This group operates independently of other Section programs and comprises a multi-divisional, dedicated staff that includes the disciplines necessary to review the entire range of information provided in a SARP. On the average, more than 20 SARPs are under consideration by ANL at any given time. The SARP is usually a voluminous document that describes the packaging technically and justifies why the packaging meets all applicable regulations.

Each SARP consists of nine chapters: General Information and Drawings, Structural, Thermal, Containment, Shielding, Criticality, Operating Procedure, Acceptance Tests and Maintenance Program, and Quality Assurance. Selected review activities are described below.

Materials

The objective of the materials review is verification that the materials of construction will maintain the package integrity under the mechanical and thermal loadings expected during both normal and hypothetical accident conditions of transport. Although no specific acceptance criteria exist for packaging materials, all materials used for construction must be documented so that the packaging can be evaluated.

As an example, O-ring seals used in the containment vessel for high-level radioactive materials are typically made from an elastomeric material. The qualification and acceptance requirements for a seal assembly in a packaging of this type are as follows:

(a) The seal material must be described by an authoritative specification, either ASTM, military (MIL), or Aerospace Material Specification (AMS). (b) Physical test evidence is required to show that the actual seal assembly is acceptable. (c) These tests must be

conducted on a full-size prototype flange-and-seal assembly or on an actual package. (d) The tests must show that the maximum leak or release rates for both the normal conditions of transport and hypothetical accident conditions are not exceeded. (e) In cases where the qualification for the normal conditions of transport leak rates is sufficient to satisfy the hypothetical accident condition release rates, an analysis is required that shows zero radial movement at the seal for all accident test conditions specified in the Code of Federal Regulations (CFR), Title 10, Part 71. (f) The tests must be conducted at the worst-case temperature and pressure occurring during normal and hypothetical accident conditions of transport. (g) The physical qualification tests need only be conducted once to verify the adequacy of the seal material and closure flange design.

Structural

Although federal regulations and guidelines issued by NRC contain some requirements that are addressed directly by structural review or analysis, the majority of the structural effort is directed toward evaluating the deformation behavior of a cask as it relates to requirements imposed in relation to other disciplines such as containment, criticality, and shielding. Structural criteria in the regulations address peripheral items, such as lifting and tiedown devices, for which performance requirements are imposed in terms of allowed stresses under specified loading conditions. The regulations also specify the maximum reduction in dimensions and volume of containers for shipping fissile materials when these containers are subjected to drop tests under defined conditions.

We have the tools to study the structures analytically and thus evaluate the packaging's ability to withstand the specified regulatory tests. Analyses can deal with loadings incurred in drop tests, movement due to thermal gradients, stresses due to differential pressure, or adequacy of attachments. Typically analyses are kept as simple as possible and use handbook closed-form solutions where applicable. However, computer solutions are used when necessary, based on PC-implemented codes whenever possible, including simple "text book" dynamic codes, general-purpose finite-element analysis codes, or an NRC/DOE-funded specialized cask analysis code called "SCANS." For more complex analyses, mainframe computer codes such as ANSYS and ADINA are available.

As an example of the analysis performed by the SARP Review Group, consider a typical packaging system for shipping radioactive material, consisting of an inner vessel to contain the product, shielding to limit external radiation, material to act as a thermal shield, an outer container, and a structure designed to absorb structural loadings due to external impact. When shipments are within the regulatory jurisdiction of DOE, the recommended design criterion for the primary containment vessel is either Section III or Section VIII, Division 1, of the ASME Boiler and Pressure Vessel Code, depending on the activity of the contents. Nevertheless, many containment vessels for radioactive packagings follow a design criterion that limits the maximum stress to some fraction of the yield strength derived with standard engineering handbook equations, i.e., a "strength of materials" design. Although a design based on this simplified criterion may be adequate to resist imposed structural loadings during normal transport conditions, the overall margins of safety against structural loadings during an accident may be insufficient to absolutely preclude a release of the contents. Consequently, the SARP Review Group compared a "strength of materials"

Schematic diagram of a prototypical high-level radioactive material packaging system

Section through a prototypical containment vessel for high-level radioactive material

design analysis to an ASME Code design analysis of a prototypical containment vessel representative of a packaging for the transport of high-level radioactive material. The figures above show a schematic diagram of the prototypical packaging system considered, and a section through the prototypical containment and outer vessels.

The study developed a comparison of (a) a design analysis based on handbook equations for calculating the stresses in a pressure vessel representing the containment structure, where the design criteria for this analysis limited the calculated stresses to some fraction of the yield strength in a "strength-of-materials" design, with (b) a second design analysis based on criteria from the ASME Code and a two-material, three-dimensional ANSYS finite-element model to evaluate the stresses. A comparison of results showed that the simplified handbook analysis predicted stresses in the lid structure that are about one-third of those obtained from the finite-element model analysis. The discrepancy was caused by the inability of the simplified analysis to account for the differential thermal expansion of the lid structure, which contained both lead and stainless steel. Additional loadings associated with the hypothetical accident fire will complicate matters and further reduce the accuracy of a simplified analysis. This can lead to a structure that is inadequate for the service loadings and that would compromise the safety of the packaging.

Thermal

The thermal review evaluates the thermal operating characteristics and performance of the package under normal transport and hypothetical accident conditions, taking into account the extreme environmental conditions, minimum and maximum decay heat loads, and damage caused by the drop and puncture tests as specified in 10 CFR §71. The review also includes confirmatory analyses; comparison of the analytical results with allowable

limits of temperature, pressure, and thermal stresses for the package components; and determination of the effect of thermal performance on the structural, containment, and shielding areas of the package.

To determine that a package complies with the CFR requirements under all transport conditions, the confirmatory analyses are focused on modeling and evaluating package performance under worst-case conditions. Normally, worst-case scenarios are too complex to model with any degree of certainty; thus a review is performed by examining the worst-case bounding conditions. An example of a review performed recently, with the HEATING6 module of the SCALE Computer Code, is described below. The SARP Review Group selected HEATING6 because it is designed specifically for thermal analysis of nuclear shipping casks. Furthermore, this module has been thoroughly tested on a set of casklike problems; has been compared with other thermal analysis codes such as TRUMP, TEMPEST, Q/TRAN, CINDA-3G etc.; and is well documented.

The packages, shown in the figure below, are designed for shipment of inner or outer unirradiated fuel elements for the High Flux Isotope Reactor (HFIR). The outer cylindrical shell, bottom, and top flat lid of the packages are fabricated from 11-gauge AISI 1010 carbon steel. The fuel load cavities are formed by stacking 1-in.-thick exterior-grade Douglas fir plywood rings in the container. Disks without holes are used in the bottom and top of the container to form the cavity. A 1-in.-thick layer of polyethylene foam lines the cavity walls, floor, and ceiling.

The containment review staff needed to know if the fuel element would melt during hypothetical accident thermal test conditions. The information was needed to ensure that the maximum quantity of material released did not exceed the CFR requirements.

Packages for HFIR fuel elements (dimensions in inches)

The structural review had concluded that there is a possibility of some tearing of the bottom plate, which could lead to wood exposure after a free-fall event. The wood exposure during a test can lead to wood burning and possible fuel melting. The thermal confirmatory analyses therefore examined the torn-at-bottom package conditions.

Modeling and computer analysis of the torn-at-bottom package is very difficult because the geometry of the worst-case tear is unknown and the wood-burning phenomena are very complex to model with any level of confidence. The thermal review was therefore made by first examining the conditions for wood burning and then performing the bounding-case analyses.

Wood burning due to natural convection was first examined. The pressure differential generated by the buoyant forces due to high-temperature gases inside the outer shell was calculated to be <0.001 psi. With negligible buoyant-force pressure differential and only a small vent area available for air inflow due to an approximately 8-in. tear, natural convection is not present to cause continuous burning of the wood after cessation of the 30-min external heat input.

As a worst-case bounding condition, an analysis was performed in which continuous wood burning inside the outer shell due to forced ventilation was assumed. A one-dimensional cylindrical model of the package (shown on the left side of the next figure) was used. The flame at the surface of the plywood ring was assumed to be at 1475°F and moving radially inward at a rate of 2 in./hr. Calculation of temperature distribution in a package showed that wood surrounding the fuel element will provide good thermal protection and that most of the heat of combustion will escape to the environment even when the outer shell acts as a thermal resistance. The analysis further showed that even when only an 0.25-in.-thick layer of wood remains to protect the inner shell, the temperature of the fuel element surface reaches only 259°F , far below the cladding melting temperature of 1080°F .

In the second bounding-case analysis, the fuel element without the wood, foam, or steel shell (right side of next figure) was exposed directly to 30 min of external heat input at 1475°F . The element was modeled as a circular cylinder consisting of a homogenized mixture of fuel and aluminum cladding with negligible thermal resistance. The analysis showed that even with direct exposure to the heat input at 1475°F for 30 min, melting of the inner and outer fuel elements will only be 17 and 9%, respectively. This melting amounts to a release of less than 0.45 and 0.61 of the limits specified in 10 CFR §71.

The bounding-case analyses of the hypothetical accident thermal event showed that the unirradiated HFIR fuel element packages, after the torn-at-bottom conditions from a free-fall, meet the containment requirements of 10 CFR §71.

Containment

The containment review evaluates (a) the integrity of the containment boundary, (b) the radioactive-leak-rate requirements for normal and hypothetical accident conditions, and (c) special double-containment requirements for plutonium shipments. The

*1-D model of package with
wood burning inside the
outer shell*

*Fuel element exposed directly to
30 min of heat flux at 1475°F*

containment review is intimately connected with the structural and thermal analyses for impact on the environment and integrity of the containment boundary.

The HFBR Fresh Fuel Shipping Container, which is designed to ship up to seven fuel assemblies, is presented as an example of a containment evaluation in which the contents provide the containment and are subjected to the tests for the normal and hypothetical accident conditions of transport per 10 CFR § 71. The radioactive contents of the HFBR Fresh Fuel Shipping Containers are limited to two unirradiated HFBR fuel assemblies containing no more than 0.07 Ci of enriched uranium, based on a maximum loading of 355 g of ^{235}U per assembly. These quantities amount to less than 0.7 of the 10 CFR §71 limit.

The containment boundary of the HFBR Fresh Fuel Shipping Container consists of the outer surfaces of the fuel plate cladding and the aluminum/cermet fuel. The containment boundary was evaluated by the "Brookhaven National Laboratory Description and General Specification for HFBR Fuel Element Type KM (May 29, 1987) provided in the SARP and the fuel-plate drawings. Thus, staff confirmatory analyses focused on whether the cladding will remain leaktight and the surface contamination will not increase during normal conditions of transport. Because the radioactive material does not exceed the specified limit, the requirements of 10 CFR §71 for the release of radioactive material during the hypothetical accident conditions of transport do not apply.

Cladding Leaktightness

The confirmatory analysis for cladding leaktightness considered three possible threats to fuel containment during transport: (a) mechanical deformation, (b) temperature, and (c) corrosion.

Mechanical Deformation

Fuel meat plates are fabricated by powder metallurgy. Fuel fines ranging in size from 100 to 325 mesh (44 to 150 μm) are homogeneously blended with aluminum alloy fines encapsulated and evenly dispersed throughout the matrix. Fuel plates are clad with ASTM B 209 alloy 6061-T6 aluminum. A metallurgical bond between the fuel meat matrix and the cladding is formed by hot rolling during fabrication. Annealed ASTM B 209 alloy 6061-T6 aluminum cladding has an allowable 25% elongation at room temperature. The ductility of the cermet meat inside the cladding decreases with the volume fraction of metal in the meat. If a fuel plate is bent, a crack in the relatively thick meat can concentrate stretching of the thin clad at that point and cause rupture. The fuel meat contains a maximum of 20.7 vol.% U_3O_8 for the HFBR fuel plates. Tests with U_3O_8 in aluminum at ORNL, as stated in ORNL/TM-7607, indicated that below 50 vol.% U_3O_8 , the aluminum matrix is continuous and the meat is ductile. Thus at 20.7 vol.% U_3O_8 , the aluminum matrix of the HFBR fuel plates is continuous and the meats are ductile. In addition, an MTR-type fuel plate, fabricated as the HFBR fuel plates, was bent up to 80° around a small radius, and the bending did not breach the cladding even though the deformation was greater than can occur even under hypothetical accident conditions.

Initial cladding integrity is verified by ultrasonic inspection and a blister test (nonbond indication) at a temperature between 475 and 493°C for every fuel plate. Acceptable bonding, defined as no visible separation between the layers when viewed at low magnification and with a minimum of 40% grain growth over an 0.25-in. interface length, is verified by destructively testing a minimum of three plates of a qualification batch of 60 plates. Metallographic sections of finished fuel plates include a longitudinal cut through each end of the fuel core for at least 1 in. and a traverse cut through the middle of the fuel core. Thereafter, delamination tests conducted on both end clippings of 2 of 24 plates verify the results of the destructive tests. The ultrasonic inspection, the blister test, and the destructive test ensure that each fuel plate is properly fabricated and is thus able to pass the extreme 80° bending test without the aluminum fusion bonds breaking and releasing contamination. Operational experience was cited in the SARP in which more than 200 fuel shipments since 1978 had no release of radioactive material. With a measurement sensitivity of ≤ 1000 dpm and a routine transfer/shipment time of 10 hr, the leak rate was found to be $\leq 0.45 \times 10^{-9}$, that of the allowable per hour limit. Therefore, the HFBR Fresh Fuel containment, which is the fuel plate cladding together with the Al-cermet fuel, satisfies the regulatory requirement for no loss of radioactive contents as specified in 10 CFR §71 for normal transport conditions.

Temperature

Irradiated MTR-type fuel plates have been heated to 500°C , as cited in the SARP, without release of fission gases, indicating that the fusion bond between the aluminum cladding and the Al/cermet fuel remain intact at high temperatures. Unirradiated fuel has not been degraded by reactor operation, and therefore the spent fuel results are a worst case with respect to containment of HFBR unirradiated fuel. The safety margin is larger still because the 108°C maximum fuel temperature cited in the SARP for HFBR unirradiated

fuel elements during normal conditions of transport is much less than the 500°C temperature of the tests. Therefore, containment will not be compromised during normal conditions of transport due to increased temperature.

Corrosion

Aluminum is a highly electropositive element and would react rapidly with oxygen or water except for a very thin but highly protective oxide film that instantly forms on any exposed fresh surface. At room temperature, this film is penetrated and the aluminum is rapidly attacked by strong alkaline solutions. Protection from such attack is provided primarily by the shipping container and secondarily by the polyethylene bag in which the assembly is sealed. Therefore, corrosion prevention meets the intent of 10 CFR §71.

Surface Contamination

Contamination remaining on the outer surfaces of the cladding after fabrication is $<0.015 \mu\text{Ci}$ for two HFBR fuel assemblies. These quantities correspond to 0.15×10^{-6} of the allowable limit. Confirmatory analysis showed that the external surface contamination with all the nonfixed fuel assembly contamination released from each individual fuel plate surface and averaged over the external cylindrical surface is $<0.05 \times 10^{-5} \mu\text{Ci}/\text{cm}^2$ for contents consisting of two HFBR fuel assemblies. This is below both the limit of $1.0 \times 10^{-5} \mu\text{Ci}/\text{cm}^2$ specified in 10 CFR §71 for any time during transport and of $1.0 \times 10^{-4} \mu\text{Ci}/\text{cm}^2$ for exclusive-use shipments by rail or highway only. The polyethylene bag in which each fuel assembly is sealed provides an additional margin of safety in preventing this contamination from reaching the external surface of the package. Therefore, the staff concludes that the HFBR Fresh Fuel Shipping Container satisfies the containment requirements of 10 CFR §71.

Shielding

Independent confirmatory analyses were performed to verify that the HFIR Spent Fuel Shipping Cask design meets CFR shielding requirements, which specify that the dose rate be $<200 \text{ mrem/hr}$ at the package surface and $<10 \text{ mrem/hr}$ at 2 m from the package surface for normal conditions of transport and $<1000 \text{ mrem/hr}$ at 1 m from the package surface during hypothetical transport accident conditions. One loading contains 17 fuel elements that were irradiated in the ORR reactor for 90 days at 30 MW power and then allowed to decay for 215 days to produce a cask decay heat level of 3.53 kW. The radioactive source strength at the end of that time was calculated with the ORIGEN-S module in the SCALE-3 computer code system, and this source in turn was input into the XSDRNP-S and XSDOSE modules in SCALE-3 to determine dose rates at the package surface and at 2 m from the package surface.

The 17 fuel elements are held in place by a steel basket (shown schematically in the next figure), which is placed in a steel cylindrical cask constructed with 7.75 in. of lead shielding around the side and bottom and 7.5 in. of lead shielding on the top. The cask was

further equipped with impact limiters on the top and bottom, and the outsides of the upper and lower impact limiters, together with the radial surface of the cask, were taken as the package surfaces. The computed dose rates for the normal conditions of transport are listed below.

Normal Conditions of Transport Dose Rates, mrem/hr

Location	Side	Top	Bottom	Allowable
At Package Surface	81	50	64	<200
2 m from Surface	5	3	4	<10

The displayed dose rates verify that the package design meets the CFR shielding requirements for normal conditions of transport. Structural confirmatory analysis verifies that the package remains intact structurally under hypothetical accident conditions of transport. With a structurally intact cask under hypothetical accident conditions, the above dose rates apply to the hypothetical accident case as well, verifying that the package design meets the shielding requirements of less than 1000 mrem/hr at 1 m from the package surface for the hypothetical accident conditions of transport.

Criticality

Independent confirmatory analyses were performed for the HFIR Spent Fuel Shipping Cask to verify that the package design meets the CFR criticality requirements that an infinite array of undamaged packages be subcritical under optimal hydrogenous moderation for normal conditions of transport and that 250 damaged packages be subcritical if stacked together in any arrangement, closely reflected on all sides of the stack by water, and with optimal interspersed hydrogenous moderation during hypothetical accident conditions of transport. Subcriticality is taken to be a k_{eff} value (plus two standard deviations) of <0.95 and was calculated with the KENO V.a module in the SCALE-3 computer code system.

One loading contains 17 irradiated ORR fuel elements held in place in a steel basket, as shown in the figure below and described in the previous subsection. Analysis showed that the casks have very little interaction because of the thick reflectors formed by the lead shielding. Structural analysis showed that the cask remains intact under hypothetical accident conditions of transport. Thus, both normal and hypothetical accident conditions could be satisfied by analyzing an infinite array of water-filled casks that touched each other

*HFIR Fuel Basket for
17 ORR Fuel Elements*

without the presence of impact limiters. The k_{eff} (plus two standard deviations) calculated under these very conservative conditions was 0.77, which is well below the subcritical upper limit of 0.95 and verifies that the package design meets the CFR requirements for subcriticality under both normal and accident conditions of transport.

Quality Assurance

A review of the SARP Quality Assurance Chapter is conducted to verify that all applicable QA requirements for the packaging and transportation of radioactive material are covered in the SARP. The QA Chapter includes provisions for control of the design, procurement, fabrication, testing, operations, and maintenance activities. Federal Regulations 10 CFR §173 (Shippers - General Requirements for Shipments and Packagings) and 10 CFR §71 (Packaging and Transportation of Radioactive Material) establish requirements for the QA Chapter in the SARP. In addition, NRC Regulatory Guide 7.10 (Establishing Quality Assurance Programs for Packaging Used in the Transport of Radioactive Material) and ASME NQA-1 (Quality Assurance Program Requirements for Nuclear Facilities) are used as guidance to establish QA requirements for the implementation of 10 CFR §71. Additional controls in the procurement section have become necessary to ensure material property conformance with packaging design requirements due to an increase in counterfeit and substandard parts in the nuclear, aerospace, and transportation industries. Because fasteners are frequently employed in critical applications for packagings, independent verification of material properties for fasteners has been incorporated into the QA Chapter to prevent the use of counterfeit or substandard parts.

At the request of DOE-HQ, select members of the ANL SARP Review Group, along with the DOE-HQ sponsor and two members from the ANL-West Environment, Safety, and Health/Quality Assurance Oversight group, conduct at DOE field office sites a two-and-one-half-day QA Workshop for SARPs to train SARP applicants to determine and include the proper QA requirements in the SARP. The objective of the workshop is to demonstrate an acceptable process for determining which QA requirements apply to a specific packaging. The QA workshop provides the applicant with valuable information for developing, establishing, and implementing an effective QA plan for a specific packaging. During the past six years, ANL has conducted 21 QA workshops at various DOE field office sites.

Transportation Technical Support

The tasks in this effort support the DOE Transportation Management Program. Present task areas are to provide transportation technical support to DOE and produce and distribute visual materials for public information and DOE training. Visual presentation through films and videos provides an effective way to inform the public and train participants on transportation issues.

The DOE Transportation Management Program has supported the production of training and public information videos and films in the past and has recently supported a

distribution program. The distribution effort has made these visual materials available to students, civic groups, and other members of the public through classroom showings and television.

The distribution of the film/video "Transportation of Radioactive and Other Hazardous Materials" is shown in the map below. The total number of viewers during the 25-month period in classrooms was 695,462. This number is certified by teachers who fill out forms after each showing. The demographics can be illustrated in many ways because all of the location and viewer information is contained in a data base. Every year questionnaires are sent out to 10% of the showing in the classroom distribution program. The map on the next page shows the 1991-92 school-year ratings on a scale of 1-10.

The film/video "Transportation of Radioactive and Other Hazardous Materials" was seen by nearly 700,000 viewers in more than 3400 locations between March 1990 and April 1992

Television has had exceptional results. The TV distribution data are not as reliable as the classroom distribution data because they are based on the number of estimated viewers derived from a formula that considers TV homes in the market area, time of day, TV channels serving the market area, and share of audience for the reporting stations. However, the exact number of telecasts is known: from the start of the program (in March 1990) to June 1992, there have been 15,706 telecasts. Total estimated viewers number more than 33 million.

Viewer ratings of the film/video "Transportation of Radioactive and Other Hazardous Materials," 1991-92

Recent Work by the Transportation of Hazardous Materials Section

Publications

D. T. Raske and Z. Wang, Application of the ASME Code in Designing Containment Vessels for Packages Used to Transport Radioactive Materials, presented at 1992 ASME Pressure Vessel and Piping Conf., June 21-25, 1992, New Orleans.

P. Turula and Z. Wang, Radioactive Material Transport Cask Seal Systems under Thermal Loadings, presented at 1991 ASME Pressure Vessel and Piping Conf., June 23-27, 1991, San Diego.

P. Turula, Z. Wang, and G. F. Popper, The Implementation and Verification of a Viscoplastic Material Model Using the ANSYS Code, Proc. ANSYS 5th Intl. Conf. and Exhibition 1991, Vol. II, May 20-24, 1991, Pittsburgh, pp. 10.19-10.23.

Appendix A: Regular MCT Employees

Administration

Staff R. W. Weeks, Division Director
 W. J. Shack, Associate Division Director
 R. A. Valentin, Associate Division Director
 W. H. Livernash, Building Manager, 212
 B. H. Malak, Financial Administration
 C. A. Malefy, Technical Editor
 A. C. Smith, Jr., Deputy Facilities Engineer, 212
 D. L. Telfer, Staff Assistant

Salaried B. K. Baudino
 J. L. Donahue

Materials Technology

	Ceramics	Corrosion	Mechanics of Materials
<i>Staff</i>	R. B. Poeppel U. Balachandran S. E. Dorris K. C. Goretta M. T. Janagan P. S. Mody J. J. Picciolo J. P. Singh C. A. Youngdahl	T. F. Kassner O. K. Chopra H. M. Chung A. B. Hull B. A. Loomis K. Natesan J. H. Park W. E. Ruther W. K. Soppet	D. R. Diercks M. C. Billone A. M. Hassanein S. Majumdar J. Y. Park J. Rest H. R. Thresh T. Wiencek S. A. Zawadzki
<i>Salaried</i>			W. F. Burke C. F. Konicek D. R. Schmitt J. R. Summers
<i>Technicians</i>	J. E. Emerson R. L. McDaniel	R. W. Clark G. M. Dragel L. J. Nowicki D. L. Rink	T. M. Galvin D. R. Perkins S. L. Phillips F. E. Soppet G. J. Talaber J. C. Tezak J. A. Zic
<i>Secretary</i>	S. M. Hagamann*	S. M. Hagamann*	P. J. Peterson
	Tribology	Irradiation Performance	
<i>Staff</i>	F. A. Nichols D. E. Busch R. A. Erck A. Erdemir G. R. Fenske	L. A. Neimark A. B. Cohen D. A. Donahue A. G. Hins Y. Y. Liu J. E. Sanecki H. C. Tsai	
<i>Salaried</i>		W. Kettman F. Pausche F. E. Saviole	
<i>Technicians</i>	R. H. Lee	D. J. Evans D. O. Pushis K. E. Stair	
<i>Secretary</i>	D. K. Moores	E. L. Hartig	

*Assigned to more than one section.

Components Technology

	Superconductivity Applications	Analytical Thermal- Hydraulics	Thermal and Mechanical Sciences
<i>Staff</i>	J. R. Hull Y. S. Cha T. M. Mulcahy R. C. Niemann K. L. Uherka	W. T. Sha M. Bottoni T. H. Chien H. M. Domanus R. C. Schmitt J. G. Sun	M. W. Wambeganss S. S. Chen S. U. Choi J. A. Jendrzeczyk K. E. Kasza
<i>Technicians</i>			A. Wantroba R. K. Smith
<i>Secretary</i>	J. A. Stephens*	S. A. Moll	J. A. Stephens*
	Instrumentation and NDE	Transportation of Hazardous Materials	
<i>Staff</i>	A. C. Raptis W. A. Ellingson G. A. Forster N. Gopalsami E. R. Koehl D. S. Kupperman W. P. Lawrence S. H. Sheen	G. F. Popper R. D. Carlson J. J. Oras, Jr. F. G. Prohammer V. L. Shah P. Turula	
<i>Salaried</i>	W. E. Brewer		
<i>Technicians</i>	R. N. Lanham		
<i>Secretary</i>	N. M. Heeg	J. L. Fisher	

*Assigned to more than one section.

Appendix B: Honors, Awards, and Professional Activities

Honors and Awards

M. C. Billone and T. F. Kassner, Winners of Argonne National Laboratory Pacesetter Award for extraordinary effort in analyzing the effects and potential problems of a leak in the Intense Pulsed Neutron Source booster target cladding (June 1992).

A. Erdemir, Recipient of Al Sonntag Paper Award for *Tribological Properties of Boric Acid and Boric-Acid Forming Surfaces Part I: Crystal Chemistry and Mechanism of Self-Lubrication of Boric Acid*, STLE Mtg., Philadelphia (May 1992).

A. Erdemir, Recipient of R&D 100 Award, *Self-Replenishing Boric Acid Films as Solid Lubricants* (1991).

D. S. Kupperman, Recipient of Federal Laboratory Consortium (FLC) Award for Excellence in Technology Transfer for 1992 (May 6, 1992).

R. H. Lee, Third Prize in 1991 Impact Through Applied Images Competition, Scientific, Technical, & Biomedical category), hosted by Professional Photographers of America, Inc., and Eastman Kodak Co.

R. H. Lee and A. Erdemir, First Prize in photomicrograph competition (Art of Tribology category) at ASME Wear of Materials Conference, Orlando, FL, and Honorable Mention (Microscopy Category) (April 8-11, 1991).

S. Majumdar, Recipient of Federal Laboratory Consortium (FLC) Award for Excellence in Technology Transfer for 1992 (May 6, 1992).

J. P. Singh, Recipient of Federal Laboratory Consortium (FLC) Award for Excellence in Technology Transfer for 1992 (May 6, 1992).

Professional Society Activities

U. Balachandran, Invited to serve as an Advisor in the International Conference Program Advisory Committee for the INTERMAG '93 Conference, Stockholm, Sweden, April 13-16, 1993.

S. S. Chen, Welding Research Council, Member, Task Force on Flow-Induced Vibration (1989 to present).

S. S. Chen, American Society of Mechanical Engineers, Chairman, Technical Subcommittee on Fluid-Structure Interactions, Pressure Vessel and Piping Division (June 1987 to present).

S. S. Chen, American Society of Mechanical Engineers, Member, Pressure Vessel and Piping Committee, Nuclear Engineering Division (1987 to present).

S. S. Chen, American Society of Mechanical Engineers, Fellow of the ASME (1987 to present).

S. S. Chen, American Society of Mechanical Engineers, Member, Technical Committee on Flow-induced Noise and Vibration, Noise Control and Acoustics Division (1987 to present).

H. H. Chung, American Society of Mechanical Engineers, Member, Pressure Vessels and Piping Committee, Nuclear Engineering Division (June 1985 to present).

W. A. Ellingson, Sigma Xi Honorary Society, Member (1978 to present).

W. A. Ellingson, American Society for Nondestructive Testing of Materials, Member (1985 to present).

W. A. Ellingson, American Society of Mechanical Engineers, Member (1985 to present).

W. A. Ellingson, American Society of Mechanical Engineers, Fellow.

W. A. Ellingson, Joint Army, Navy, NASA, Air Force (JANNAF), Member, Subcommittee on Nondestructive Evaluation.

W. A. Ellingson, American Association of Physicists in Medicine, Member (1989 to present).

K. C. Goretti, Board Member, Materials Science and Engineering Alumni Association, 1990-1991, College of Engineering, University of Illinois at Urbana-Champaign.

B. J. Hsieh, American Society of Mechanical Engineers, Member, Technical Committee on Vibration and Sound Design Engineering Division (1989-1990).

A. B. Hull, Representative for ANL at Industry Day sponsored by Society of Women Engineers (Nov. 2, 1991).

J. R. Hull, American Society of Mechanical Engineers, Secretary, American Society of Mechanical Engineers (ASME) Superconductivity Technical Committee in Advanced Energy Systems Division.

J. R. Hull, Illinois Solar Energy Association, Member, Board of Directors (1988-1991).

J. R. Hull, American Society of Mechanical Engineers, Papers Review Chair, ASME Superconductivity Technical Committee in the Advanced Energy Systems Division (1988 to present).

K. E. Kasza, American Society Mechanical Engineers, Member, American Society Mechanical Engineers (ASME) Committee on Fluid Transient (1987 to present).

P. S. Maiya, TMS-AIME, Member, Nuclear Metallurgy Committee (1986 to present).

S. Majumdar, American Society of Mechanical Engineers, Member, Subgroup on Elevated Temperature Design of the Boiler and Pressure Vessels Code Committee (1988 to present).

T. M. Mulcahy, American Society of Mechanical Engineers, Member, Technical Subcommittee on Fluid-Structure Interactions, Pressure Vessels and Piping Division (1987 to present).

T. M. Mulcahy, American Society of Mechanical Engineers, Member, Special Working Group on Dynamic Analysis, Code Committee (1980 to present).

K. Natesan, ASM International, The Materials Information Society, Member, Journal of Materials Engineering Committee (1990-1993).

K. Natesan, National Association of Corrosion Engineers, Vice Chairman, Committee on Materials for Fossil Fuels Combustion and Convection Systems (1989 to present).

J. Y. Park, American Society for Testing and Materials, Member, Committee F04 on Medical and Surgical Materials (1981 to present).

J. Y. Park, American Society for Testing and Materials, Member, Committee E24 on Fracture Testing of Materials (1979 to present).

J. Y. Park, American Society for Testing and Materials, Chairman, Subcommittee G1.08 on Corrosion of Nuclear Materials (1983-1990).

A. C. Raptis, Institute of Electrical and Electronics Engineers, Member, IEDM-IEEE Detectors, Sensors and Displays Subcommittee.

P. Turula, Institute of Nuclear Materials Management, Member, INMM/ANSI-N14 Standards Committee for Packaging and Transportation of Radioactive Materials (1987 to present).

M. W. Wambsganss, American Society of Mechanical Engineers, Member, Technical Committee on Flow-induced Noise and Vibration, Noise Control and Acoustics Division (1983 to present).

M. W. Wambsganss, American Society of Mechanical Engineers, Member, Codes and Standards Committee, Subgroup on Vibration Monitoring of Internals, Task Group to Prepare Heat Exchanger Vibration Standard (1983 to present).

Other Committee Participation

U. Balachandran, Judge/Timekeeper DOE High School Science Bowl, ANL (Feb. 29, 1992).

U. Balachandran, Science Fair Judge, Our Lady of Peace School, Darien, IL (Jan. 27, 1992).

U. Balachandran, Invited to serve on committee to examine Ph.D. dissertation at Northwestern University (Jan. 6, 1992).

U. Balachandran, Science Fair Judge, Avery Coonley School, Downers Grove, IL (Feb. 6, 1992).

M. C. Billone, Chairman, Materials and Components Technology Division Social Committee (January 1989 to present).

M. C. Billone, Chairman, Materials and Components Technology Division Library Committee (1987 to present).

M. C. Billone, Member, DOE/OFE International Thermonuclear Experimental Reactor Design Team (October 1987 to present).

Y. S. Cha, Member, MCT Safety Committee (1989 to present).

Y. S. Cha, Member, Materials and Components Technology Division Social Committee (January 1989 to present).

U. S. Choi, Member, M.S. Thesis Committee, School of Mechanical Engineering, Purdue University (1989 to present)

U. S. Choi, Member, International Energy Agency District Heating and Cooling Advanced Fluids Experts Group (1987 to present).

S. E. Dorris, Member, Ph.D. Thesis Committee, Dept. of Materials Science and Engineering, Northwestern University (1988 to present).

S. E. Dorris, Chairman, Building 212 Safety Committee (1989 to present).

S. E. Dorris, Member, Illinois Ceramics Advisory Group (1988 to present).

W. A. Ellingson, Chairman, Session IB - Ceramics, Conference on Fossil Energy Materials, Oak Ridge, TN (May 1991).

W. A. Ellingson, Member, Materials and Components Technology Division Education Committee (1986 to present).

W. A. Ellingson, National Committee, Oak Ridge National Laboratory team for DOE funding areas.

W. A. Ellingson, Member, National Committee, DOE Fossil Energy National Task Force Leader for Coal Gasification Materials.

W. A. Ellingson, Member, Honorable Harris W. Fawell's Science and Technology Advisory Committee.

W. A. Ellingson, Member, Thrust Group on Image Reconstruction and Processing, University of Chicago Center for Imaging Science (1988 to present).

A. Erdemir, Member, Space and Naval Warfare Systems Command (SPAWAR) Evaluation Panel for IR&D Projects (1990 to present).

K. C. Goretta, Science Fair Judge, Our Lady of Peace School, Darien, IL (Jan. 27, 1992).

K. C. Goretta, Secretary, American Ceramic Society Section Officers (1992).

K. C. Goretta, M.S. Thesis Defense Committee Member - Yue Fang, U. of Illinois at Chicago (July 1991).

K. C. Goretta, Member, M.S. Thesis Committee, Metallurgical and Materials Engineering Department, Illinois Institute of Technology (1989 to present).

A. G. Hins, Member Bldg. 212 Safety Committee, May 1991-March 1992.

A. G. Hins, Member IPNS New Booster Target Design Group (August 1991-March 1992).

B. J. Hsieh, Member, Materials and Components Technology Division Safety Committee, (1986-1990).

K. E. Kasza, Member, DOE National Technical Working Group on Heavy Water Reactor Thermal Hydraulics (1989 to present).

K. E. Kasza, Member, Ph.D. Thesis Committee, University of Illinois at Chicago (1989 to present)

K. E. Kasza, ANL Program Coordinator for District Heating and Cooling (1986 to present).

K. E. Kasza, ANL Program Coordinator for Fossil Energy Core Program, Energy Transport Processes Mechanisms (1987 to present).

K. E. Kasza, Member, ANL Multiphase Flow Research Institute Steering Committee (1985 to present).

K. E. Kasza, Organizer and Chairman, International Energy Agency District Heating and Cooling Advanced Fluids Experts Group (1987 to present).

D. S. Kupperman, Member, U.S. Nuclear Regulatory Commission Task Group on Digitization of Industrial Radiographs. Coordinated the Task Group effort in producing the NRC report *Review and Evaluation of Technology, Equipment, Codes and Standards for Digitization of Industrial Radiographic Film* (NUREG-1452, May 1992).

W. H. Livernash, Member, Environmental Planning and Review Committee-NEPA Revision (1989 to present).

W. H. Livernash, Member, Pressure Vessel Safety Committee (1988 to present).

W. H. Livernash, Member, AMOS Customer Group (1988 to present).

W. H. Livernash, Member, SAR Review Committee for ATLAS Upgrade Project (1988 to present).

W. H. Livernash, Member, Plant Facilities and Services Advisory Committee (1988 to present).

W. H. Livernash, Member, Advanced Photon Source Safety Committee (1986 to present).

P. S. Maiya, Member, Intense Pulsed Neutron Source Enriched Target Safety Review (1988 to present).

P. S. Maiya, Member, Nuclear Systems Materials Handbook Working Group, MP-1 (1987 to present).

C. A. Malefy, Coordinator, MCT Open House activities (1991).

C. A. Malefy, Coordinator, MCT ES&H Training (1991 to present).

C. A. Malefy, Representative, MCT Division Technology Transfer (1990 to present).

C. A. Malefy, Volunteer Editor, Publications Committee, Society for Technical Communication (1990 to present).

C. A. Malefy, Member, ANL Copier Management Advisory Committee (1991-1992).

A. I. Michaels, Member, Government Steering Committee for DOE-ECUT-sponsored ACTIS (A Computerized Tribological Information System) program (1987 to present).

K. Natesan, Member, TMS AIME.

K. Natesan, Chairman of NACE Committee T2F: Fossil Fuel Systems.

K. Natesan, Member, ASM International Heat Resistant Materials Committee.

F. A. Nichols, Member, ASM Atomic Transport and Flow & Fracture Activities (1989 to present).

J. J. Oras, Materials and Components Technology Division Quality Assurance Representative.

J. J. Oras, Member Materials and Components Technology Division Area Safety Committee.

J. J. Oras, Alternate Member of N14 Standards Committee, Packaging and Transportation of Radioactive Materials, for American National Standards Institute (ANSI).

J. Y. Park, Member, Subcommittee E10 on Nuclear Technology and Applications, American Society for Testing and Materials (1992 to present).

A. C. Raptis, Member, Advisory Council for the College of Engineering, University of Akron (1990).

J. Rest, Member, MCT Promotion Committee (1990 to present).

J. Rest, Member, Advanced Photon Source Users Representatives from ANL and The University of Chicago (1989 to present).

J. Rest, Member, Materials and Components Technology Division Computer Committee (1986 to present).

J. P. Singh, Appointed as Adjunct Professor of Metallurgical and Materials Engineering for 1991-92 academic year, Illinois Institute of Technology.

J. P. Singh, Organized technical program for Symposium on Ceramic Matrix Composites, held at American Ceramic Society 93rd Annual Meeting and Exposition, Cincinnati (April 28-May 2, 1991).

D. L. Telfer, Member, ACA Publicity Subcommittee (1990 to present).

D. L. Telfer, Chairman, ACA Fund Raising Subcommittee (1988 to present).

D. L. Telfer, Member, Argonne Combined Appeal Steering Committee (1988 to present).

H. R. Thresh, Member, ANL Cathode Processor Design Review Committee (1988 to present).

H. R. Thresh, Member, Intense Pulsed Neutron Source Booster Design Committee (1988 to present).

H. R. Thresh, Member, LILY Target Design Review Committee (1988 to present).

P. Turula, Member, American Society of Mechanical Engineers, Boiler Code Section III, Subcommittee on Nuclear Packaging (NUPACK); and working group on design for Nuclear Packaging (1990 to present).

P. Turula, Member, INMM/ANSI-N14 Standards Committee for Packaging and Transportation of Radioactive Materials (1987 to present).

K. L. Uherka, Member, DOE/HQ Technical Evaluation Committee for Reviewing Small Business Research Initiative proposals.

K. L. Uherka, Member, DOE/CH Technical Review Board for Reviewing Industrial Heat Pump proposals.

K. L. Uherka, Member, MCT 300-Area Safety Committee.

K. L. Uherka, Member, Joint ANL/NASA-LeRC Task Force on Aerospace Applications of High-Temperature Superconductivity (1988 to present).

K. L. Uherka, Ad Hoc Member, Materials and Components Technology Division Computer Committee (1986 to present).

K. L. Uherka, Chairman, Materials and Components Technology Division 300-Area Safety Committee (1986 to present).

M. W. Wambsganss, Member, Committee on Heat Transfer and Heat Exchangers, International Energy Agency, Program of Energy Conservation (1978 to present).

M. W. Wambsganss, Associate Member, Shellside Flow and Vibration Subcommittee, Heat Transfer Research, Inc. (1988 to present).

Invited Teaching and Research at Other Institutions

W. A. Ellingson, Adjunct Professor, Medical Physics, Chicago Medical School (1987 to present).

N. Gopalsami, Joint Research, Applied Physics Department, U.S. Army Tank-Automotive Command, Warren MI (1987 to present).

J. R. Hull, Invited Member, Texas Solar Pond Consortium, Research Advisory Board.

J. R. Hull, Member, Research Advisory Board, Texas Solar Pond Consortium (1989 to present).

J. Y. Park, Adjunct Professor, Department of Civil Engineering, Mechanics and Metallurgy, University of Illinois at Chicago (1988 to present).

Invited Conference Participation

U. Balachandran, Symposium on Ceramic Superconductors, 2nd International Ceramic Science and Technology Congress, Orlando, FL, November 13, 1990: Program Chairman.

H. M. Chung, 9th International Conference on Zirconium in the Nuclear Industry, Kobe, Japan, Nov. 5-8, 1990: Session Organization and Paper Selection Committee.

W. A. Ellingson, Chairman, Session 3B: Computerized Tomography at 5th International Symposium on Nondestructive Characterization of Materials, Karuizawa, Japan, May 27-30, 1991.

W. A. Ellingson and R. A. Belz (Sverdrup Tech., Inc.), Magnetic Resonance Imaging Applications to Rocket Propulsion Systems, Organized Workshop and hosted Panel Discussion, 1991 JANNAF Nondestructive Evaluation Subcommittee Meeting, Kennedy Space Center, May 13, 1991.

W. A. Ellingson, Chairperson Session IB - Ceramics at 5th Annual Conference on Fossil Energy Materials, Oak Ridge, TN, May 14, 1991.

W. A. Ellingson, Conference on Modern Ceramics Cosponsored by American Ceramic Society and the American Society for Nondestructive Evaluation, July 9-12, 1990, Columbus, OH: Program Cochairman.

W. A. Ellingson, Symposium on Advanced Tomographic Imaging Methods for the Study of Materials, Fall 1990 MRS Meeting, Boston, MA, Nov. 26-Dec. 1, 1990: Organizer.

J. R. Hull, Magnetic Bearing Symposium, Intersociety Energy Conversion Engineering Conference, Reno, NV, Aug. 1990: Organizer.

K. E. Kasza, Cooling and Load Management Using Ice Slurry Generation, Pipe Transmission, and Storage in Distributed Network Systems, Invited Member of Instructional Staff of Workshop on Ice Slurry District Cooling, Minneapolis, May 11-12, 1992.

D. Kupperman, Workshop on Application of Neutron Diffraction to the Determination of Residual Stresses in Engineering Materials, Argonne National Laboratory, May 1990: Co-organizer.

T. M. Mulcahy, Division J, Structural Dynamics of Extreme Load Analysis, SMIRT-11, Tokyo, Aug. 1990: Coordinator.

R. B. Poeppel, High-Temperature Superconductors, Satellite Symposium 4 of 7th CIMTEC World Ceramics Congress, Montecatini Terme, Trieste, Italy, July 2-5, 1990: Member, International Advisory Committee.

R. B. Poeppel, Superconductivity: The Manufacturing Challenges, Chicago, Oct 16-18, 1990: Conference Advisory Committee.

Editorial Activities

U. Balachandran, Reviewer, Grant Application No. 20177-92-I, High- T_c Superconductor Push-Pull Transimpedance Amplifier for Particle- and Nuclear-Detector Electronics, U.S. Department of Energy.

U. Balachandran, Reviewer, Physica-C: Superconductivity, Thermodynamic Study for the Effects of . . .

S. S. Chen, ACTA Mechanica Solida Sinica, Member of International Advisory Editorial Board, Pergamon Press and Huazhong University of Science and Technology.

J. R. Hull, Associate Editor, Solar Ponds (Solar Energy) (1986 to present).

D. S. Kupperman, Associate Technical Editor, Materials Evaluation (ASNT journal) (1986 to present).

M. T. Lanagan, Reviewer, Applied Physics Letters, Superior microwave properties . . . (1992).

M. T. Lanagan, Reviewer, Superconductor Science and Technology.

M. T. Lanagan, Reviewer, Journal of the American Ceramic Society, Effect of Composition on Superconducting Properties in the System Ba-Y-Gd-Cu-O (Dec. 1991).

M. T. Lanagan, Reviewer, Superconductor Science and Technology, Properties and microstructures of powder-melting-processed . . . (Dec. 1991).

M. T. Lanagan, Reviewer, BiPbSrCaCuO superconductor prepared by a . . . (Nov. 1991).

K. M. Nair (E. I. duPont de Nemours Co.), U. Balachandran, Y.-M. Chiang (Massachusetts Institute of Technology), and A. S. Bhalla (Pennsylvania State U.), Editors, Proc. Symp. on Superconductivity and Ceramic Superconductors at 2nd International Ceramic Science and Technology Congress, Orlando, FL, Nov. 12-15, 1990, The American Ceramic Society; Ceramic Transactions, Vol. 18, Westerville, OH (1991).

K. Natesan and D. J. Tillack, Editors, Heat-Resistant Materials, Proceedings 1st International Conference on Heat Resistant Materials, Sept. 23-26, 1991, Fontana, WI, ASM International, Materials Park, OH.

R. B. Poeppel, Reviewer, Applied Physics Letters, American Institute of Physics Superconducting Ceramics of $\text{Bi}_2\text{Sr}_2\text{Ca}_1\text{Cu}_2\text{O}_x$ Prepared by Heating in a Vacuum-Sealed Vessel (Jan. 1992).

R. B. Poeppel, Reviewer, Journal of Applied Physics and Applied Physics Letters, Superconducting Properties of $(\text{Bi,Pb})_2\text{Sr}_2\text{Cu}_3\text{O}_x$ Tapes (Sept. 1991).

K. L. Uherka, Reviewer, Journal of Applied Physics and Applied Physics Letters: Superconductor Application (1988 to present).

Program Index

Acoustic Leak Detection and Location: 123

Advanced Neutron Source: 52, 56, 60, 79, 97

Advanced Photon Source: 87, 106

Arms Control and Nonproliferation: 1, 112, 113

Basic Energy Sciences, DOE: 1, 103

Casting Modeling: 98

Coating by Physical Vapor Deposition: 66-68

COMMLX Code: 93-96

Conservation and Renewable Energy, DOE: 1, 104, 116

Cryostat Current Leads: 85

DARPA: 120

Defense, U.S. Dept. of: 1

Diamond and Diamondlike Coatings: 68, 70

District Heating and Cooling: 105

EBR-II: 60, 77

Electric Power Research Institute: 105

Environment, Safety and Health, DOE: 1

Fast-Flux Test Facility: 77

Flow-Induced Vibrations: 103

Fossil Energy, DOE: 1, 7, 35-37, 100, 114

Fusion Energy, DOE: 1, 37-41, 79

Ice Slurries for District Cooling: 105

Industrial Technology, DOE: 117

Integral Fast Reactor: 1, 2, 10, 38, 52, 59, 77

Intense Pulsed Neutron Source: 58

International Thermonuclear Experimental Reactor: 38, 52, 57, 58, 108

Ion-Beam-Assisted Deposition: 66

Light-Water Reactors: 1, 10, 31-34, 54, 55, 87

Magnetic Bearings: 86

Magnetic Levitation (Maglev) Systems: 107

Multiphase Flow and Heat Transfer: 104

National Maglev Initiative: 107

National Park Service: 1

National Science Foundation: 1

National Tribology Program: 3

Nuclear Energy, DOE: 1

Nuclear Regulatory Commission: 1, 31, 52, 78, 94, 129

Reduced-Enrichment Research and Test Reactor: 52, 59

Safety Analysis Reports for Packaging (SARPs): 129-138

Solid Oxide Fuel Cell: 115

Superconductivity Pilot Center: 2, 85

Transportation, U.S. Dept. of: 2, 129

Transportation Management, DOE: 138

Transportation Materials, DOE: 66, 70

Transportation Technologies, DOE: 66

Tribological Testing: 68

Ultrasonic Imaging and NDE: 113-115, 123

VICTORIA Code: 56

END

**DATE
FILMED**

2 / 2 / 93