NRTSC

NUCLEAR REACTOR TECHNOLOGY
AND SCIENTIFIC COMPUTATIONS

Keywords: MODERATOR
SHIELD WATER
WATER CHEMISTRY
CORROSION
STAINLESS STEEL
REACTOR
PTERM
REACTOR MATERIALS PROGRAM

Retention - Permanent

**ASSESSMENT OF SUSCEPTIBILITY
OF TYPE 304 STAINLESS STEEL
TO
INTERGRANULAR STRESS CORROSION CRACKING
IN
SIMULATED SAVANNAH RIVER REACTOR
ENVIRONMENTS(U)**

By

R. S. ONDREJCIN *R. S. Ondrejcin*
G. R. CASKEY, JR. *G. R. Caskey, Jr.*

ISSUED: DECEMBER 1, 1989

Authorized Derivative Classifier

J. M. Stone

J. M. Stone
MTS Manager

12/12/89

Date

SRL SAVANNAH RIVER LABORATORY, AIKEN, SC 29808
Westinghouse Savannah River Company

Prepared for the U. S. Department of Energy under Contract DE-AC09-88SR18035

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

PROJECT: REACTOR MATERIALS PROGRAM

DOCUMENT: WSRC-RP-89-1230

TITLE: ASSESSMENT OF SUSCEPTIBILITY
OF TYPE 304 STAINLESS STEEL TO
INTERGRANULAR STRESS CORROSION
CRACKING IN SIMULATED SAVANNAH RIVER
REACTOR ENVIRONMENTS (U)

TASK: 89-023-G-1

APPROVALS

N.G. Awadalla
N. G. AWADALLA, MANAGER

DATE: 12/12/89

J. M. Stone
J. M. STONE, MANAGER

DATE: 12/12/89

E. W. Baumann
E. W. BAUMANN, TECHNICAL REVIEWER

DATE: 12/07/89

Allan Zagrobnik
RQAP APPROVAL

DATE: 12/17/89

INTRODUCTION

The experimental investigation discussed in the attached report(1) was one of several related tasks in the Reactor Materials Program (RMP) intended to integrate laboratory corrosion tests with chemical and electrochemical characterization of the moderator and thermal shield water in an operating reactor(2). The goal of these corrosion studies is a moderator chemistry technical manual which will provide the technical bases for water chemistry control to reduce corrosion of the stainless steel in the moderator (process water) system and the thermal shields.

Investigation of intergranular stress corrosion cracking (IGSCC) of sensitized Type 304 stainless steel was one task in a contract between the Savannah River Site (SRS) and General Electric Nuclear Energy, San Jose, California that covered stress corrosion cracking and fracture assessment for the moderator piping and the reactor tanks(3). Two related tasks in the General Electric contract have been completed and reports are being prepared. The first was designed to measure crack growth rates of sensitized specimens to complement the present study. The second was designed to evaluate the stress corrosion response of specimens that had been irradiated in the High Flux Isotope Reactor at the Oak Ridge National Laboratory. Fluence levels were comparable to those estimated for the reactor tank walls. The latter experiments apply to corrosion of irradiated stainless steel in the reactor tanks.

The stress corrosion response of sensitized Type 304 stainless steel was evaluated under specified temperature and water chemistry conditions that encompassed the conditions encountered by the moderator and thermal shield water. Test conditions did not cover all possible extreme conditions that might be encountered during protracted shutdowns or layups. None of the specimens in this investigation had been irradiated. Specimens were machined from a section of process water piping removed from R-reactor. Details of the machining, chemical analysis of the section and cutting diagrams are contained in an earlier report(4). A detailed description of the constant extension rate tensile (CERT) test equipment, methods, results and the statistical analysis of the data are contained in the General Electric report(1).

This summary report reviews the major experimental findings of the investigation and discusses how the findings may be applied to control of moderator and shield water chemistry. The principal product of the statistical analysis is an equation which predicts the relative susceptibility of Type 304 stainless steel to IGSCC under any combination of water chemistry and temperature conditions within the ranges of the test variables. This relation allows a comparison of the relative aggressiveness of combinations of water chemistry conditions likely to be met within the bulk moderator and the thermal shield water during normal reactor operation or shutdown.

Based on evaluation and interpretation of the experimental results, recommended guidelines have been prepared with the goal of minimizing IGSCC within the stainless steel components of the process water and thermal shield systems.

RECOMMENDED GUIDELINES

A practical approach for reducing IGSCC in the process water piping is through improvement in the methods for reduction and control of chloride and sulfate concentrations in the moderator. The goal concentrations for chloride and sulfate are 2 and 7 parts per billion (ppb, i.e. $\mu\text{g/L}$), respectively. Specific recommendations include:

- evaluate ion exchange practices in the light water reactor industry to assure SRS is using the best resins in the H and OH form;
- eliminate sources of radiolytically degradable materials that contain chlorides or sulfates that can enter the reactor tank;
- remove materials from the moderator system that contain leachable chlorides, such as gaskets, and filters.

Purification of the thermal shield water is recommended. Addition of ion exchange systems to reduce chloride and sulfate anion concentrations to 5 ppb and 7 ppb respectively, would extend the residual life of the shield water systems. An alternative is to increase the size of the heat exchanger to reduce the water temperature.

SUMMARY

The IGSCC effects of temperature (40-120°C) and the concentrations of chloride (Cl^- , 2-100 ppb), sulfate (SO_4^{2-} , 7-500 ppb), carbon dioxide (CO_2 , 20-1000 ppb), oxygen (O_2 , 100-8000 ppb) and hydrogen peroxide (H_2O_2 , 400-5000 ppb) were measured in aqueous solutions. Two series of statistically designed CERT experiments were performed, one with all the independent variables except H_2O_2 and the other series with all the independent variables except O_2 , but with the O_2 from the decomposition of H_2O_2 measured.

A multiple regression analysis of the data resulted in an equation that relates IGSCC to the three effective independent variables: temperature, Cl^- and SO_4^{2-} . The CO_2 and O_2 effect on IGSCC did not change over the concentrations and temperature ranges studied. Hydrogen peroxide was deleterious, but when the Cl^- concentration was at or below 8 ppb, the deleterious effect of H_2O_2 was no longer seen, only the effect of Cl^- on cracking. Reduction of Cl^- to 2 ppb was significant (statistically) in reducing IGSCC compared to 8 and 30 ppb. Sufficient reduction of Cl^- therefore had a two fold effect, elimination of the peroxide effect and decrease of the Cl^- effect on IGSCC.

The potential for IGSCC was measured as the logarithm of the adjusted time to maximum stress (LATMS) and included factors for both the ductility and strength of the steel under test. On a relative basis, the higher the value of LATMS the more favorable the water chemistry.

The relationship of LATMS to T, Cl^- and SO_4^{2-} was determined for a peroxide medium. The equation and examples of its application are given in the Discussion section.

The variables that decreased IGSCC in order of decreasing importance were $T > \text{Cl}^- > \text{SO}_4^{2-}$. For example, the value for adjusted time to maximum stress (ATMS) under maximum operational impurity limits for moderator ($T=100^\circ\text{C}$, $\text{Cl}^-=30$ ppb, $\text{SO}_4^{2-}=50$ ppb) is 30 hours, while under nominal conditions, ($T=100^\circ\text{C}$, $\text{Cl}^-=10$ ppb, $\text{SO}_4^{2-}=25$ ppb), ATMS is 70 hours. The reduction in moderator temperature to 60°C was beneficial as far as IGSCC was concerned and increased ATMS to 140 hours for maximum impurity concentrations. If Cl^- and SO_4^{2-} were reduced from SRS maximum to about double nominal for a Boiling Water Reactor ($\text{Cl}^-=2$ ppb, $\text{SO}_4^{2-}=7$ ppb) at 100°C the ATMS would be 280 hours. This is a large improvement approaching no IGSCC in sensitized 304 stainless steel which was measured at about 400 hours.

In process water piping, a series of specific recommendations were made that included: 1) evaluate light water reactor ion exchange systems compared to those at SRS to lower the Cl^- and SO_4^{2-} in the moderator by modification of the SRS ion exchange system, 2) eliminate sources of radiolytically degradable materials that contain chlorides and are used in the reactor tank, 3) remove Cl^- leachable materials used in other parts of the moderator system, and 4) improve the lower limits of detection for Cl^- and SO_4^{2-} .

With respect to improving the lifetimes of the thermal shields, the recommendation was made to add ion exchange systems to purify the water to $\text{Cl}^-=5$ ppb and $\text{SO}_4^{2-}=7$ ppb or to increase the flow through or the size of the thermal shield heat exchangers to reduce temperatures from 70 to 45°C .

DISCUSSION

Experimental Approach

Special water circulation loops were built to provide controlled environments that simulated SRS aqueous systems. The following variables were controlled and measured in real time: T at 40 - 120°C , Cl^- at 2 - 100 ppb, SO_4^{2-} at 7 - 500 ppb, O_2 at 100 - 8000 ppb, H_2O_2 at 400 - 5000 ppb and CO_2 at 20 - 1000 ppb. These variables had been previously identified by analyses of the reactor aqueous systems at SRS. The ranges chosen exceeded those measured in the reactor. Nitric acid was added to maintain pH at 5.1 ± 0.2 .

Initial Testing

Preliminary tests were performed to insure that a statistical design could be applied to evaluate the test variables. In the ranges proposed, the fracture surfaces of test specimens changed from 100% ductile to 100% IGSCC, an excellent situation for a statistical design. A difficulty was encountered when testing at a combination of high T, low O_2 and high H_2O_2 . The H_2O_2 decomposed to O_2 and H_2O , leading to high

O₂ and the inability to conduct tests with high H₂O₂ and low O₂. Consequently, the test was divided into two subgroups, one with controlled O₂ and no H₂O₂ and one with controlled H₂O₂ and measurement of the O₂ released.

Experimental Design And Predictive Equation

The statistical design chosen was a two tier central composite (response surface) matrix. One tier resulted in an O₂ model, the other in a H₂O₂ model. Each model included a linear part to determine coefficients for the main interactive effects which measure the level and twist of the response surface. Each model also included a quadratic part to determine coefficients for second order effects of the independent variables which describe the curvature of the response surface. Every data point was run in at least duplicate.

The logarithm of the adjusted time to maximum stress (LATMS) was chosen as the dependent variable signifying IGSCC. This variable included the time to maximum stress and ductility as measured by both elongation and reduction in area combined. Prediction equations were then evaluated for the O₂ tests and the H₂O₂ tests. Since H₂O₂ is always present in SRS reactors, even with the reactors shut down, the data for the peroxide case is the one of interest. Statistically significant coefficients were determined by multiple regression analyses and resulted in the following equation for peroxide containing solutions.

$$\begin{aligned} \text{LATMS} = & -0.1553 (\text{Cl}^-)^{0.43815} - 0.03646 (\text{T}) - 1.799 (\text{SO}_4^{-2}) - 0.18508 \\ & + 0.04071 (\text{T}) (\text{SO}_4^{-2}) - 0.18508 \\ & - 0.3285 (\text{Cl}^-)^{0.43815} (\text{SO}_4^{-2}) - 0.18508 \\ & + 0.02149 [(\text{Cl}^-)^{0.43815}]^2 \\ & + 4.993 \end{aligned}$$

where: LATMS is the logarithm of time in hours

Cl⁻ and SO₄⁻² are in ppb and

T is temperature in °C

With the above equation the following table was developed illustrating the relative advantages of operating with various conditions of moderator impurity levels and temperature. In this table a value about ≥ 400 hours for ATMS is a condition where no IGSCC will occur in sensitized 304 stainless steel.

Evaluation Of Reactor Conditions

	Maximum Impurity D ₂ O	Nominal D ₂ O	50% of Nominal Power	SRS Pure D ₂ O	Shield Water	Cooled Shield Water	Pure Shield Water
Cl ⁻ (ppb)	30	10	30	2	100	100	5
SO ₄ ⁻² (ppb)	50	25	50	7	300	300	7
T (°C)	100	100	60	100	70	45	70
ATMS (hours)	30	70	140	280	100	360	300

From the results, the obvious way to increase the lifetimes of the reactors is to improve the water purity in both the reactors and the thermal shield systems to the operational levels seen in power reactors. The shield systems could be improved about an equivalent amount if larger shield water heat exchangers were installed to lower the water temperature from 70 to 45°C. If flow through the present shield heat exchangers can be increased sufficiently, the same effect would be observed. Note that the data indicate the process water system should crack more frequently than the shield system which has been the case.

Relative Importance Of Independent Variables

The critical F value (the value that gives the lower bound of significance) at the 90% confidence level was 2.9 for evaluation of the H₂O₂ model. The terms of the equation in order of decreasing significance were T with an F value of 90, Cl⁻ with 48, SO₄⁻² with 7.3, (Cl⁻)² with 4.7 and the (Cl⁻) (SO₄⁻²) cross product with 3.1. In the H₂O₂ model, SO₄⁻² by itself or squared was not significant. The independent variables that affected IGSCC in order of decreasing importance were therefore T > Cl⁻ > SO₄⁻².

Temperature, the most significant variable, increased cracking as it increased. Under test conditions, IGSCC started when the water temperature was between 40 and 55°C.

The presence of H₂O₂ is an important variable that increases susceptibility to cracking, but over the range studied (400-5000 ppb), variations in concentration made no variation in cracking. Presumably, levels would have to be below 400 ppb to decrease susceptibility to cracking.

H₂O₂ was detrimental when Cl⁻ was above 30 ppb but there was no peroxide effect when Cl⁻ was present at concentrations of 8 and 2 ppb. Decreasing the Cl⁻ from 8 to 2 ppb also decreased the severity of cracking substantially. SO₄⁻² by itself was not significant, but there was the strong interaction of (T) and (SO₄⁻²) that became more detrimental as the temperature increased.

Electrochemical potential (ECP) has been shown to have an effect on IGSCC. The SRS reactors operate between 400-600 mV vs a standard hydrogen electrode.⁵ In the tests, the potentials were within the reactor range validating the tests data.

In the concentration ranges studied, the O₂ (100-8000 ppb) and CO₂ (20-1000 ppb) effect on IGSCC did not change when the temperature ranged from 40-120°C.

Significance Of Results To SRS Reactors

The experimental results indicate that the most significant way to reduce IGSCC susceptibility would be to reduce moderator temperature during operation. Additional consideration may be given to various methods to accomplish this, e.g. more efficient heat exchangers than those presently in the system.

The second most significant way is to reduce the Cl⁻ concentration of the coolant below its nominal value of 10 ppb. Sources of the Cl⁻ may be degradation of residual chlorinated hydrocarbons on aluminum components, the asbestos after-filter on the ion exchange columns, or other unknown sources.

The third significant way is to reduce SO₄⁻² below its present nominal value of ~25 ppb. The only known source of this ion is from degradation of sulfonated ion exchange resin fines that might get past the after-filters of the mixed bed ion exchangers.

Specific Guidelines For Improving Water Purity And Increasing Time To IGSCC

- Changes are recommended in the ion exchange system.
 - 1) Compare SRS ion exchange to power reactor operation.
 - 2) Replace asbestos after filters with stainless steel screens.

Power reactors use stainless steel screens to prevent loss of fractured ion exchange resins, SRS uses asbestos that can leach Cl⁻. The only known source of SO₄⁻² in the moderator is from irradiation of fractured sulfonated ion exchange resin that has gotten past the after filters. Power reactors sometimes use finely divided ion exchange resin for final ionic removal. Flow rates and resin size in SRS reactors should be evaluated.

- A concerted effort should be made to reduce and accurately measure chloride.
 - 1) Substitute "Flexicarb" for "Flexitalic" gaskets
 - 2) Eliminate the use of "Scotch Cast" epoxies in applications such as automated temperature monitors
 - 3) Remove organic residues from aluminum clad components without the use of chlorinated compounds.
 - 4) Improve lower limits of detection for Cl⁻ and SO₄⁻².

Low levels of Cl⁻ (8 ppb or less) eliminate the deleterious effects of H₂O₂ and reduce its effects on IGSCC.

"Flexitalic" gaskets are made with African blue asbestos which releases chlorides. "Scotch Cast" epoxies contain 1000-2000 ppm chlorine that can be released as chloride ion if irradiated sufficiently. Chlorinated hydrocarbons were used for degreasing aluminum components, then a switch was made to freon, a chlorinated and fluorinated compound. Consideration is being given to oxidizing the organic off the components rather than degreasing which is probably the best alternative of the three methods as far as introduction of impurities into the reactor is concerned. The Reactor Chloride Exclusion Committee has held walk-down inspections to identify chloride sources. The committee issued a set of recommendations to aid in the exclusion of chloride sources from the process water system.⁶

Present lower limits of detection by the laboratories for Cl^- is 10 ppb and for SO_4^{2-} about 25 ppb. Sampling and off-line analyses can contaminate samples to these levels. To be assured that the analyses are correct an on-line ion chromatograph should be installed to follow water chemistry in one reactor as a minimum but preferably in all reactors. A custom designed analyzer is in the process of being installed in K-reactor that has other features in addition to an ion chromatograph.⁷ When operational, this instrument would meet the needs for water analyses in K area.

Shields

- Install an ion exchange system to lower Cl^- to 5 ppb and SO_4^{2-} to 7 ppb.
- Increase flow through or increase heat exchanger size to reduce the water temperature from 70 to 45°C.

Either of these would be effective.

The guidelines in this section would increase the lifetimes of the moderator piping and shields by statistically lowering the possibility of IGSCC initiation in the heat affected zones of welds.

RSO/GRC/sgm
SRL-EDG-890156

REFERENCES

1. P. Aldred, W. L. Clarke and S. A. Wilson, "Assessment of the IGSCC Susceptibility of Sensitized, Nonirradiated Type-304 Stainless Steel in Simulated SRP Environment Using the CERT Technique," General Electric Co., San Jose, CA, November 1987.
2. Reactor Materials Program, DPST-84-820, edited by N. G. Awadalla, G. R. Caskey, Jr., and R. S. Ondrejcin, E. I. du Pont de Nemours and Co., Aiken, SC, December 1984.
3. Reactor Materials Program Progress Report, WSRC-RP-89-1021, Compiled by N. G. Awadalla, G. R. Caskey, Jr., and R. L. Sindelar, Westinghouse Savannah River Co., Aiken, SC, September 1989.
4. Reactor Materials Program, Materials Source History for Type 304 Stainless Steel Testing Program, DPST-88-1010, by K. J. Stoner, E. I. du Pont de Nemours and Co., Aiken, SC, December 1988.
5. Electrochemical Potentials of Stainless Steel and Platinum In K-Reactor Moderator, DPST-88-621, TO: J. M. Stone, FROM: E. W. Baumann and R. S. Ondrejcin, July 6, 1988.
6. Results of Walk-Down Inspections of P and K Reactors by the Reactor Chloride Exclusion Committee, WSRC-RP-89-1078, by P. E. Zapp, Westinghouse Savannah River Co., Aiken, SC, October 27, 1989.
7. Reactor Materials Program Progress Report, July 1987 to June 1989, WSRC-RP-89-1021, compiled by N. G. Awadalla, G. R. Caskey, Jr., and R. L. Sindelar, Westinghouse Savannah River Co., Aiken, SC, September 30, 1989.

J. D. Spencer
Page 9
December 1, 1989

WSRC-RP-89-1230
TASK # 89-023-G-1

ATTACHMENT NO. 1

AX-681981
PTERM
GE-87-033

Stress Corrosion and Fracture Assessment Program
Dupont/GE Letter Contract No. AX-681981

Topical Report for Task A
Nonirradiated CERT Tests

Title

Assessment of the IGSCC Susceptibility of
Sensitized, Nonirradiated Type-304 Stainless
Steel in Simulated SRP Environments Using the
Constant Extension Rate Tensile (CERT) Technique

November 1987

Prepared by: Peter Aldred
P. Aldred, W.L. Clarke and S.A. Wilson
Plant Materials Technology
M/C 751

Reviewed by: Peter Aldred
P. Aldred, Senior Program Manager
BWR Technology Programs
M/C 751

Approved by: G.M. Gordon
G.M. Gordon, Manager
Nuclear Fuels & Plant Materials Technology
M/C 768

Disclaimer

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, produce, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or services by trade name, mark manufacturer or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or agency thereof.

Assessment of the IGSCC Susceptibility
of Sensitized, Nonirradiated Type-304
Stainless Steel in Simulated SRP
Environment Using the CERT Technique

November 1987

P. Aldred

W.L. Clarke

S.A. Wilson

General Electric Co.

San Jose, Ca.

Table of Contents

	<u>Page</u>
EXECUTIVE SUMMARY.....	E-1
1.0 INTRODUCTION AND OBJECTIVES.....	1-1
2.0 TEST TECHNIQUE.....	2-1
3.0 EXPERIMENTAL DETAILS.....	3-1
3.1 Materials.....	3-1
3.2 CERT Test.....	3-2
3.3 SRP Environment Simulation.....	3-3
3.3.1 Water Circulation Loops.....	3-3
3.3.2 Chemical Analyses.....	3-5
3.3.2.1 Anion Dionex Ion Chromatography System.....	3-6
3.3.2.2 Hydrogen Peroxide Analyzer.....	3-7
3.3.2.3 Carbon Dioxide Analyzer.....	3-8
3.4 Electrochemical Potential (ECP) Measurements.....	3-9
3.5 Post-Test Specimen Examination.....	3-10
4.0 TEST CONDITIONS.....	4-1
4.1 Option 1.....	4-1
4.2 Statistical Experiment Design: The Central Composite Design.....	4-2

Table of Contents

	<u>Page</u>
4.3 Low Chloride-Sulphate Test Extension.....	4-10
4.4 Shield Water Environment Tests.....	4-11
5.0 TEST RESULTS AND DISCUSSION.....	5-1
5.1 Option 1.....	5-1
5.1.1 CERT Tests.....	5-1
5.1.2 ECP.....	5-2
5.1.3 Hydrogen Peroxide/Oxygen/Temperature Study	5-2
5.2 CERT Results from Central Composite Design, Low Chloride-Sulphate Test Extension, and Shield Water Environment Tests.....	5-3
5.2.1 Central Composite Design.....	5-3
5.2.2 Low Chloride-Sulphate Test Extension.....	5-3
5.2.3 Shield Water Environment.....	5-4
5.2.4 Electrochemical Potential (ECP).....	5-4
5.3 Statistical Analysis of Results.....	5-5
5.3.1 Introduction.....	5-5
5.3.2 Analysis of the Oxygen Design Results.....	5-8
5.3.2.1 Oxygen Model Derivation.....	5-8
5.3.2.2 Graphical Representation of the Adopted Oxygen Model.....	5-13
5.3.2.3 Importance of Individual Variables in the Adopted Oxygen Model.....	5-17

Table of Contents

	<u>Page</u>
5.3.3 Analysis of the Peroxide Design Results and the Low Chloride-Sulphate Results.....	5-25
5.3.3.1 Hydrogen Peroxide Model Derivation....	5-25
5.3.3.2 Graphical Representation of the Adopted Hydrogen Peroxide Model.....	5-31
5.3.3.3 Importance of Individual Variables in the Adopted Hydrogen Peroxide Model...	5-37
5.3.4 Additional Studies.....	5-41
5.3.4.1 Results of Option 1 Tests and their Correlation with the Hydrogen Peroxide Model and Oxygen Model.....	5-41
5.3.4.2 Validation of the Hydrogen Peroxide Model.....	5-42
5.3.4.3 Loop Effect in the Hydrogen Peroxide Environment.....	5-43
5.3.4.4 Effect of ECP-SS Alone.....	5-45
5.3.4.5 Repeatability of Oxygen and Hydrogen Peroxide Data.....	5-46
5.3.5 Summary of Data Analysis and Interpretation....	5-47

Table of Contents

	<u>Page</u>
6.0 SUMMARY, FULFILLMENT OF OBJECTIVES AND CONCLUSIONS.....	6-1
6.1 Summary.....	6-1
6.2 Fulfillment of Objectives.....	6-7
6.3 Conclusions.....	6-8
7.0 REFERENCES.....	7-1
Appendices:	
A. Examples of all Data Collected for Specimen 2A41	
During CERT Test for Period 4/25-4/28/87.....	A-1
B. Main Variable Chemical Analyses Plotted Within.....	B-1
the Established Tolerance Limits	

LIST OF TABLES

	<u>Page</u>
3-1 Chemical Composition of CERT Specimen Material (SRP Archive 16-inch Diameter Pipe - Ring 2A).....	3-11
3-2 Test Program Variable Concentration Measurement Range.....	3-12
4-1 Environmental Variable Levels for Option 1 Tests.....	4-12
4-2 Terms whose Coefficients can be Estimated, Oxygen Designs.	4-13
4-3 Terms whose Coefficients can be Estimated, Hydrogen Peroxide Designs.....	4-14
4-4 Pattern of Confounding of Coefficient Estimates in the Linear Parts of the Designs.....	4-15
4-5 Test Conditions for Oxygen and Hydrogen Peroxide Linear Designs, Coded Levels.....	4-16
4-6 Test Conditions for Oxygen and Hydrogen Peroxide Quadratic Designs, Coded Levels.....	4-17
4-7 Physical Levels Related to Coded Levels, Oxygen and Hydrogen Peroxide Designs.....	4-18
4-8 Test Conditions for Low Chloride-Sulphate Test Extension, Hydrogen Peroxide Environment.....	4-19
5-1 CERT Test Results for Option 1 Study.....	5-54
5-2 Task A. Linear Oxygen Design CERT Test Results.....	5-55
5-3 Task A. Linear Hydrogen Peroxide Design CERT Test Results.....	5-56
5-4 Task A. Quadratic Oxygen Design CERT Test Results.....	5-57

LIST OF TABLES (Continued)

	<u>Page</u>
5-5 Task A. Quadratic Hydrogen Peroxide Design	
Test Results.....	5-58
5-6 CERT Test Results for Low Chloride-Sulphate	
Test Extension.....	5-59
5-7 CERT Test Results for Shield Water Environments.....	5-60
5-8 Test Results: Oxygen Linear Design.....	5-61
5-9 Test Results: Oxygen Quadratic Design.....	5-62
5-10 Test Results: Hydrogen Peroxide Linear Design.....	5-63
5-11 Test Results: Hydrogen Peroxide Quadratic Design.....	5-64
5-12 Test Results: Low Chloride-Sulphate Test Extension.....	5-65
5-13 Test Results: Option1, Hydrogen Peroxide and	
Oxygen Environments.....	5-66
5-14 Quality of Fit and Coefficients in Adopted Oxygen	
and Hydrogen Peroxide Models.....	5-67
5-15 Definitions and Statistical Properties of	
Individual Parts of Equation (5-1).....	5-68
5-16 Derivation of Lower and Upper 90% Confidence Limits	
for Total Slope of LATMS over each Variable in	
the Adopted Oxygen Model.....	5-69
5-17 Derivation of Lower and Upper 90% Confidence Limits	
for Total Slope of LATMS over each Variable in	
the Adopted Hydrogen Peroxide Model.....	5-70

LIST OF TABLES (Continued)

	<u>Page</u>
5-18 Derivation of 90% Confidence Interval, Upper Limit, for delta LATMS.....	5-71
6-1 The Quantitative Importance of each Variable in Reducing IGSCC Susceptibility as a Factor in Increasing ATMS at Selected Points; and Region of Importance of each Variable.....	6-11

ILLUSTRATIONS

	<u>Page</u>
3-1 Schematic of SRP Archive Pipe (Type 304-Sch. 40) Showing Sectioning for Specimen Fabrication (Ring 2A - Side A).....	3-13
3-2 Test Specimen used for SRP CERT Program.....	3-14
3-3 Typical Sensitized Microstructures in the Simulated Weld and Furnace Sensitized CERT Specimens.....	3-15
3-4 VNC Non Irradiated Material CERT Test Facility.....	3-16
3-5 View of Recirculation Module Constructed for the SRP Corrosion Test Program.....	3-17
3-6 Schematic Diagram of the CERT Test Loop.....	3-18
3-7 Chemical Analysis Console used for the SRP Corrosion Test Program.....	3-19
3-8 Chemical Analysis Module Automated Sampling System.....	3-20
3-9 Chemical Analysis Instrumentation Subsystem Configuration.....	3-21
3-10 Typical Chemical Analysis Chromatogram.....	3-22
3-11 Typical Trendgraph for Nitrate and Sulphate During an SRP CERT Test.....	3-23
3-12 Typical Trendgraph for Chloride During an SRP CERT Test...	3-24
3-13 Typical Trendgraph for Carbon Dioxide During an SRP CERT Test.....	3-25
3-14 Typical Trendgraph for Hydrogen Peroxide During an SRP CERT Test.....	3-26

ILLUSTRATIONS (Continued)

	<u>Page</u>
3-15 Schematic of Reference and Working Electrodes used for SRP CERT Test Program.....	3-27
4-1 Transform Equations.....	4-20
4-2 Relationships between Physical and Coded Scales.....	4-21
5-1 Option 1 CERT Test Results.....	5-72
5-2 CERT Specimens after Testing in: (a) Variable High Levels and, (b) Variable Low Levels.....	5-73
5-3 Fracture Surface of Specimen 2A96 CERT Tested in Variable High Level Environment.....	5-74
5-4 Fracture Surface of Specimen 2A21 CERT Tested in Variable Low Level Environment.....	5-75
5-5 IGSCC in CERT Specimens Tested at 120°C in (a) High, and (b) Low Level Environments.....	5-76
5-6 Load-Time Curve for Option 1 CERT Specimens Tested in Various Environments.....	5-77
5-7 ECP vs Time for Loop C Showing Rapid Response and Sensitivity to Increase in HNO ₃ Concentration.....	5-78
5-8 ECP vs Time for Loop B Showing Rapid Response and Sensitivity to the Addition of H ₂ O ₂	5-79
5-9 Hydrogen Peroxide-Oxygen-Temperature Relationship.....	5-80
5-10 Range of Electrochemical Potentials Measured at SRL Compared to GE Laboratories.....	5-81

ILLUSTRATIONS (Continued)

	<u>Page</u>
5-11 Temperature Dependence of ECPs Measured at Various Oxygen-Hydrogen Peroxide Concentrations.....	5-82
5-12 Relationship of Ductility to Log Time to Maximum Stress...	5-83
5-13 Relationship of Maximum Stress to Log Time to Maximum Stress.....	5-84
5-14 Relationship of Log Time to Failure to Log Adjusted Time to Maximum Stress.....	5-85
5-15 Test Results and Fitted Model for the Oxygen Designs (Adopted Oxygen Model) (two sheets).....	5-86
5-16 Confidence Limits on Y/X_1 for a Surface where the X_2 Test Data and Operating Region is in the Region where X_2 is Important.....	5-87
5-17 In Adopted Oxygen Model, Region of Importance of TEMPC....	5-88
5-18 In Adopted Oxygen Model, Region of Importance of SO4C.....	5-89
5-19 In Adopted Oxygen Model, Region of Importance of CO2C.....	5-90
5-20 Test Results and Fitted Model for the Hydrogen Peroxide Designs (two sheets).....	5-91
5-21 Test Results and Fitted Model for the Hydrogen Peroxide Designs and the Low Chloride-Sulphate Test Extension (3 sheets).....	5-92
5-22 Effect of Temperature on LATMS, Adopted Oxygen and Hydrogen Peroxide Models.....	5-93

ILLUSTRATIONS (Continued)

	<u>Page</u>
5-23 Comparison of Predictions by Adopted Oxygen and Hydrogen Peroxide Models.....	5-94
5-24 In Adopted Hydrogen Peroxide Model, Region of Importance of CLC.....	5-95
5-25 In Adopted Hydrogen Peroxide Model, Region of Importance of SO ₄ C.....	5-96
5-26 Test Results and Values Predicted by the Adopted Hydrogen Peroxide Model, for Option 1 Testing.....	5-97
5-27 Relationship of Concentration of Oxygen by Dissociation to Hydrogen Peroxide Concentration.....	5-98
5-28 Relationship of ECP-SS to Log Adjusted Time to Maximum Stress, Oxygen Designs.....	5-99
5-29 Relationship of ECP-SS to Log Adjusted Time to Maximum Stress, Hydrogen Peroxide Designs and the Low Chloride-Sulphate Test Extension.....	5-100

Acknowledgement

The authors gratefully acknowledge the contribution made by the following individuals:

R.S. Dahlin - Water recirculation module construction
G.E. Dunning - Metallography
J.M. Huff - Computer programming (IBM)
C.W. Jewett - Computer programming (HP)
B.A. McAllister - Ion chromatography
W.H. Receiving - Chemical analysis module
M.N. Robles - Ion chromatography
J.L. Simpson - Ion chromatography
G.L. Smith - Loop operation and CERT testing
J.E. Weber - Electrochemical potential measurements

ABSTRACT

Intergranular stress corrosion cracking (IGSCC) of Type 304 stainless steel was evaluated by constant extension rate tests (CERT) of specimens machined from Savannah River Plant (SRP) decontaminated process water piping. Special water loops were constructed to provide and control environmental simulation of SRP environments (except irradiation), on-line chemical analysis module measured concentrations of chloride, sulphate, nitrate, hydrogen peroxide and carbon dioxide in real-time; other instrumentation measured oxygen, pH, conductivity, temperature and electrochemical potential (ECP).

The results from 12 preliminary CERT tests verified that IGSCC occurred over a wide range of simulated SRP environments. Seventy three specimens were tested in two pre-planned statistical experimental designs of the central composite class. In one design, testing was done in environments containing hydrogen peroxide; in the other design, hydrogen peroxide was omitted but oxygen was added to the environment. Prediction equations relating IGSCC to temperature and environmental variables were formulated from the test results. Temperature was the most important independent variable. IGSCC was severe at 100°C to 120°C and a threshold temperature between 40°C and 55°C was identified below which IGSCC did not occur. In environments containing hydrogen peroxide, as in SRP operation, a reduction in chloride concentration from 30 to 2 parts per billion (ppb or micrograms per liter) also significantly reduced IGSCC. A reduction in sulphate concentration from 50 ppb to 7 ppb was effective in reducing IGSCC provided the chloride concentration was 30 ppb or less and temperature was 95°C or higher. The presence of hydrogen peroxide in the environment increased IGSCC except when chloride concentration was 11 ppb or less. The actual concentrations of hydrogen peroxide, oxygen and carbon dioxide did not affect IGSCC.

Large positive ECP values (+450 to +750 mV Standard Hydrogen Electrode (SHE)) were measured in the simulated SRP environments containing hydrogen peroxide and these measurements are in good agreement with ECP measurements made in SRP reactors. This imparts confidence that the simulated environments used in this work are representative of SRP reactor environments.

The overall results of the CERT test suggest that the most effective method to reduce IGSCC in SRP process water piping is to reduce chloride and sulphate concentrations to as low a value as practicable.

EXECUTIVE SUMMARY

The experimental work and results described in this report cover Task A, "Non-irradiated Constant Extension Rate Tests (CERT)" which is part of the Stress Corrosion and Fracture Assessment Program (AX-681981).

The need for the work:

Over the last thirty-five years, intergranular stress corrosion cracking (IGSCC) has been observed occasionally in the Type 304 stainless steel piping and other components of the process water system (PWS) at the Savannah River Plant (SRP). The observed IGSCC occurred in weld heat affected zones and flame washed regions of the piping. In this respect, the SRP experience parallels that seen in many Light Water Reactors (LWRs) over the last two decades; however, at SRP the rate of cracking has been much lower. In the SRP process water piping, about 900 welds have been ultrasonically inspected (covering three reactors) and partially through wall cracks were found in approximately 7% of the weld heat affected zones.

Many scientific and engineering studies have been performed to understand the IGSCC mechanism in LWRs. A triad of conditions are concurrently necessary for IGSCC to occur: material condition (sensitized microstructure); over yield tensile stress (applied plus residual); and a conducive environment (oxygenated water). The SRP reactor environment contains relatively high oxygen and hydrogen peroxide levels (1 ppm (parts per million or milligrams per liter) and 2 ppm, respectively) at much lower

temperature and pressure than LWRs ($100^{\circ}\text{C}/5$ psig (pounds per square inch gauge) versus $288^{\circ}\text{C}/1050$ psig for a Boiling Water Reactor (BWR)). Also, the SRP reactor coolant has higher conductivity than the BWR coolant (3 microsiemen/cm versus 0.3 microsiemen/cm). The higher conductivity of the SRP reactor coolant is attributed primarily to nitric acid which is added to minimize corrosion of aluminum fuel cladding. Impurities such as carbon dioxide, sulphate and chloride are present also. For this combination of low operating temperature and mixed environment, the main driving force for IGSCC in weld sensitized Type 304 stainless steel is not understood. An experimental program was designed to study the effects of these environmental variables.

The work described in this report was undertaken in response to this program and identifies and ranks the environmental variables which promote IGSCC in the SRP environment. One objective was to develop an analytical model (a mathematical equation) for predicting IGSCC. The application of the model would identify an "improved" environment for SRP reactor operation.

Scope of the Experimental Work:

The experimental work was designed to simulate SRP conditions (except irradiation) as closely as possible. Test specimens were machined directly from decontaminated pipe taken from the primary loop of a shutdown SRP reactor. These test specimens were heat treated to produce sensitized grain boundaries as found in piping weld heat affected zones. Special

water circulation loops were constructed which allowed the following SRP defined environmental variables to be controlled within the test ranges given:

TABLE E-1

SRP defined environmental variable	Test range		
	<u>Low</u>	<u>Nominal</u>	<u>High</u>
Temperature (°C)	33-37	95-105	115-125
Chloride (ppb)	1-3	24-36	85-115
Sulphate (ppb)	2-6	40-60	450-550
Oxygen (ppb)	80-100	900-1100	7200-8800
Hydrogen Peroxide (ppb)	300-500	1800-2200	4500-5500
Carbon Dioxide (ppb)	15-30	270-330	900-1100

In addition, nitric acid was added to the test loops to control pH within the range 5.1 plus or minus 0.2. A state-of-the-art chemical analysis unit, having the capability of real-time on-line monitoring of test loop water chemistry, was constructed. The unit contained an ion chromatography system for anion (chloride, sulphate and nitrate) analysis, an hydrogen peroxide analyzer and a carbon dioxide analyzer. The water circulation loops were connected to autoclaves attached to Instron machines (used as slow strain rate tensile machines). Two autoclaves per test loop allowed

CERT test duplication for a given environment. The chemical analysis unit was connected to three water circulation loops and was programmable to enable data to be taken from any loop in any sequence. Thus, it was possible to run three independent environmental tests and collect data from each. IBM-Personal Computers were used to collect, store and retrieve data for detailed evaluation from: (1) the chemical analysis unit, (2) the Instron test machines, i.e. load-time data, and (3) electrodes specially built to measure the electrochemical potential (ECP) of the test environments. Initially, twelve CERT tests (Option 1) were conducted to: (1) confirm that IGSCC could be produced in sensitized Type 304 stainless steel at the test strain rate of $4.4 \times 10^{-7} \text{ sec}^{-1}$ in a nominal SRP environment; and, (2) to determine IGSCC over the range of SRP environments, i.e. using low, medium and high concentrations of the environmental variables Table E-1. These initial tests showed that hydrogen peroxide in the environment partially dissociated to produce oxygen. A detailed study of the hydrogen peroxide/oxygen concentrations as a function of temperature was performed. The results from this study were used to define two statistical experiment designs. All test conditions were identified before any testing was started. Seventy three CERT tests were completed and statistically evaluated in these planned experimental designs which were of the "central composite" class. The experimental designs called for testing at preselected combinations of levels of the variables. The model for predicting IGSCC in SRP environments was developed from these tests.

Summary of Results:

The results from the Option 1 tests showed that temperature and environment had a strong effect on IGSCC. At a low temperature, 35°C, there was no IGSCC in any environment tested, including the highest concentrations of variables anticipated in SRP reactors. In contrast, at 120°C IGSCC was severe in all environments including the lowest concentrations of variables anticipated in SRP reactors; however, IGSCC was more severe at high concentrations than at low concentrations. IGSCC also occurred in nominal SRP environments: (1) at the maximum process water temperature of 100°C, specimens exhibited 100% intergranular fracture; (2) at 78°C, specimens exhibited 94-98% intergranular fracture. When hydrogen peroxide was not included in the environment at 78°C, IGSCC decreased, indicating a detrimental effect of hydrogen peroxide.

The Option 1 testing also showed that oxygen was generated in the environment due to hydrogen peroxide dissociation. The study of hydrogen peroxide/oxygen concentrations as a function of temperature showed that as temperature increased, the degree of hydrogen peroxide dissociation increased resulting in higher oxygen concentrations. The significance of this finding was that both hydrogen peroxide and oxygen concentrations could not be controlled independently in a single experimental design. Therefore, two detailed experimental designs were developed. One design, termed the "oxygen design", was based on environments without hydrogen peroxide but with oxygen added as a gas. The second design, termed the "hydrogen peroxide" design, was based on environments with hydrogen

peroxide, the oxygen from dissociation was measured.

It was necessary to select a CERT parameter (measure of IGSCC) for use in the statistical analyses of test data. Load versus time is recorded continuously during a test, an illustration is shown in Figure E-1 for two hypothetical tests (A and B). Test A failed in a short time due to IGSCC whereas the longer time test B did not exhibit IGSCC. Thus, time to failure is one CERT parameter on which statistical analysis could be based. Test specimen ductility is reflected by post-test measurement of percentage elongation and percentage reduction of area, both of these are also CERT parameters. With reference to Figure E-1, test A would have low ductility due to IGSCC but, in contrast, test B would exhibit high ductility. Time to maximum stress (load/specimen cross sectional area), as shown by T_A and T_B in Figure E-1, is another CERT parameter.

To reflect IGSCC response, each CERT parameter and combinations of parameters (time to failure, time to maximum stress, percentage elongation and percentage reduction of area) were evaluated statistically to determine their correlation with the test environmental variables (temperature, concentrations of chloride, sulphate, hydrogen peroxide, oxygen and carbon dioxide). The combination of time to maximum stress and ductility (elongation and reduction of area) best reflected IGSCC response and was selected as the parameter to be used in the statistical analyses and development of an analytical model.

Using values of this parameter obtained from each CERT in the respective

experimental designs (oxygen design and hydrogen peroxide design), linear multiple regression analyses were performed and statistically significant coefficients estimated by a least squares criterion. From these analyses, analytical models (mathematical prediction equations) for each experimental design were obtained. These models predict IGSCC as a function of temperature and environmental variables within the temperature range and concentration ranges evaluated in the tests.

In both models, temperature was the statistically most significant variable, IGSCC increased with increasing temperature. IGSCC did not occur at 40°C, in agreement with the Option 1 results at 35°C described above, but IGSCC was predominant at 55°C. Therefore, the temperature threshold for IGSCC in SRP environments, based on CERT tests conducted with an extension rate of 1.2 mils/hour, lies between 40°C and 55°C. The temperature of the SRP coolant returning to the reactor, after passing through heat exchangers, is close to this temperature range and IGSCC has been observed in the process water piping between the heat exchangers and the reactor.

In the hydrogen peroxide model (environments containing hydrogen peroxide as in normal SRP operation), the concentration of chloride was highly significant; decreasing chloride decreased IGSCC. Decreasing the chloride concentration from 30 ppb in the nominal SRP environment to as low a concentration as possible would be beneficial; the results showed 2 ppb chloride to be less detrimental than 8 ppb on IGSCC. When hydrogen peroxide was not present in the environment, the chloride concentration did

not have a significant effect on IGSCC, as shown by the oxygen design testing. In the hydrogen peroxide model, the coefficient on the sulphate main effect term was not significant, this indicates that a change in sulphate concentration did not on average significantly affect IGSCC. However, there were significant interactions between sulphate and temperature, and between sulphate and chloride which did affect IGSCC. A reduction in sulphate concentration at a temperature of 105°C (approximates SRP operating temperature) reduced IGSCC whereas a sulphate concentration reduction at 55°C did not significantly affect IGSCC. Also, reduced IGSCC occurred with sulphate concentration reductions when the chloride concentration was at a low level as compared to when chloride was at a high level. Therefore, there would be a benefit (decreased IGSCC) if sulphate concentration was decreased to a low level, especially at normal SRP operating temperature (about 100°C) and if the chloride was concurrently decreased to as low a level as possible.

This work shows reducing the concentration of a variable may be of limited effectiveness in reducing IGSCC, depending on the level of that variable itself and the level of other variables. An "importance analysis" was performed to address this question. A variable is deemed to be important if a change in its level causes a change in IGSCC that is statistically significant. For the hydrogen peroxide model described above, the importance analysis showed that: (1) a reduction in chloride concentration is important when the initial concentration of chloride is 30 ppb or less and this applies for all levels of the other variables, (2) a reduction in sulphate is important when the chloride concentration is 30 ppb or less and

temperature is greater than 95°C; this applies over all levels of the other variables, and (3) a reduction in temperature is important over all levels of all variables.

Both the oxygen and hydrogen peroxide models, show that the presence of hydrogen peroxide increased IGSCC when chloride concentration was greater than 11 ppb. However, although the presence of hydrogen peroxide increased IGSCC susceptibility, the degree of susceptibility was not affected by the concentration of hydrogen peroxide in the range 400 to 5000 ppb. The presence or concentration of oxygen did not affect IGSCC susceptibility in either the oxygen or hydrogen peroxide design testing. This was not expected as dissolved oxygen is a main contributor to IGSCC of stainless steel in LWR high purity water environments at high temperatures (>120°C). The results showed that in the simulated SRP environments, the addition of oxygen as a gas, from hydrogen peroxide dissociation, or as a combination of the two were of equal effect. The large positive electrochemical potential (ECP) measured in the simulated SRP environments (+450 to +700 mV(SHE) when hydrogen peroxide was present) may have had an overriding effect. This range of ECP values is in good agreement with measurements made in SRP reactors. This fact is important because it lends credence to the CERT results obtained on this test program.

Significance of Results to SRP Reactor Operation:

Objectives of the CERT tests were: (1) to identify and rank environmental variables which promote IGSCC in the SRP environment, and (2) to define

prediction equations for IGSCC. These objectives were achieved and prediction equations were obtained for SRP environments containing hydrogen peroxide and for environments without hydrogen peroxide.

In both these environments, a reduction in temperature reduced IGSCC of sensitized Type 304 stainless steel. Therefore, a reduction from the normal operating temperature of 100°C would be beneficial, but overall reactor operational constraints may preclude a reduction in temperature. In SRP environments that contain hydrogen peroxide, the second most important variable was chloride concentration. This was followed by sulphate whose effect on reducing IGSCC was dependent on temperature and chloride concentration. The results showed that a marked reduction in IGSCC could be achieved by decreasing chloride and sulphate concentrations as low as possible. Reduction of chloride concentration from a nominal 30 ppb to 2 ppb and sulphate concentration from a nominal 50 ppb to 7 ppb or less would be beneficial. These reductions should be achieved by installation and proper operation of a demineralizer system. The results further showed that removal of hydrogen peroxide from the environment would reduce IGSCC provided chloride concentration was greater than 11 ppb. If chloride were reduced below this level there would be no reason to eliminate hydrogen peroxide.

Follow on Work:

The experimental work in this report identified SRP environmental variables which effectively reduced IGSCC of sensitized Type 304 stainless steel and

ranked them according to their effectiveness. Prediction equations were obtained whereby IGSCC could be related to temperature and environmental variable concentrations. This knowledge will be used in the non-irradiated crack growth rate testing in Task B. Testing will be performed to determine if the same changes in the important environmental variables, which reduced IGSCC in the CERT tests, also produce slower crack growth rates. Also, the observation that reducing chloride and sulphate concentrations to as low a level as possible will be factored in to selecting the "improved SRP environment" for the qualifying pipe test in Task C. Finally, the results from the CERT tests can be used for guidance in changing the SRP reactor environment with the objective of reducing IGSCC of the process water piping.

Figure E-1 Illustration of Load/Time Data for Two Hypothetical CERT Tests.

1.0 INTRODUCTION AND OBJECTIVES

Over the last thirty-five years, intergranular stress corrosion cracking (IGSCC) has been observed occasionally in the Type 304 stainless steel piping and other components of the process water system (PWS) at the Savannah River Plant (SRP). The observed IGSCC occurred in weld sensitized heat affected zones (HAZ) and flame washed regions of the piping. In this respect, the SRP IGSCC experience parallels that which has occurred in Boiling Water Reactors (BWRs) over the last two decades.

Over the last decade, however, the BWR IGSCC problem has become widespread. It was initially observed in small diameter piping but eventually large diameter (up to 26-inch diameter) recirculation piping experienced IGSCC. In this time period, the General Electric Company (GE) has performed many research and development programs and has gained a full technological understanding of the IGSCC mechanism in sensitized Type 304 stainless steel. Several IGSCC mitigation techniques were developed including identification and application of (1) improved IGSCC resistant materials, (2) weld residual stress improvement techniques, and (3) BWR environmental changes. Because of the expertise gained during these research and development programs, GE was contracted by Savannah River Laboratory personnel to establish and conduct a comprehensive corrosion test program. The program established by GE and SRP is essentially divided into two parts:

- (1) stress corrosion cracking studies in SRP-type environments
- (2) fracture mechanics assessment of SRP tanks and piping systems.

this report addresses part 1, the Stress Corrosion Cracking Studies.

There are three major objectives for the SRP stress corrosion cracking program:

- (1) Identify and rank environmental variables which promote and/or aggravate IGSCC in sensitized Type 304 stainless steel subjected to SRP environments;
- (2) Establish the influence of irradiation on the crack growth rate in sensitized Type 304 stainless steel subjected to SRP environments;
- (3) Verify that weld improvement techniques such as heat sink welding (HSW) and last pass heat sink welding (LPHSW), are effective in promoting residual compressive stress in "thin" walled SRP piping. Demonstrate effectiveness of these techniques, applied to weld joints between Type 304 and low carbon and nuclear grade stainless steels, by pipe testing in SRP environments.

The GE technical program to achieve these objectives is divided into the following six tasks:

- Task A: Non-irradiated Constant Extension Rate Tests (CERT)
- Task B: Non-irradiated Constant Load Crack Growth Testing
- Task C: Pipe Testing (4-Inch Diameter Pipe)
- Task D: Boiling Magnesium Chloride Testing (16-Inch Diameter Pipe)

Task E: Irradiated CERT

Task F: Irradiated Constant Load Crack Growth Testing

This report gives the results of Task A, which was based on a statistically designed experimental approach with the objectives: (1) to identify SRP environment variables which significantly affect IGSCC resistance of simulated weld sensitized Type 304 stainless steel, and (2) to obtain prediction equations which might lead to an "improved" environment for reactor operation.

2.0 TEST TECHNIQUE

Task A was conducted by performing Constant Extension Rate Tensile (CERT) tests in a range of SRP environments. The CERT test was used since it is a widely accepted test for rapidly screening variables which affect the IGSCC of Type 304 stainless steel in actual and simulated nuclear reactor coolant environments^{1,2}. The CERT tests were conducted using three, special water chemistry-controlled circulation modules fabricated specifically for these tests. The water chemistry of each module was controlled and monitored on a real time basis using a chemical analysis module also specially constructed for this program. In addition, electrochemical potential (ECP) measurements were obtained during each test so that the environment could be related to the CERT results, and comparisons made between the test environments and actual SRP environments (ECP measurements also acquired by SRL workers).

Initially, a number of CERT tests (Option 1) were conducted to: (1) confirm that IGSCC could be produced in sensitized Type 304 stainless steel in a nominal SRP environment; and, (2) to provide an understanding for scoping the SRP environments (low, medium, high concentrations of identified variables) to be used in the more extensive Task A studies. This second objective verified that SRP environments could be simulated in the laboratory, and led to a special study of the environmental interaction between hydrogen peroxide/oxygen and temperature. This special study provided information which was used to plan the Task A CERT tests on a statistical basis.

3.0 EXPERIMENTAL DETAILS

3.1 Materials

The CERT specimens were machined from the wall of a 16-inch diameter, Type-304 stainless steel pipe which was archive material from which the original plant process water lines were fabricated. The specimens were removed from the pipe in an axial direction as shown in Figure 3-1. The chemical composition of the pipe material is given in Table 3-1. The specimens for CERT testing were machined into uniaxial, flat configurations with the dimensions given in Figure 3-2. Each Specimen was identified by metal stamping both tab ends with a number preceded by "2A" to correspond to the ring from which they were sectioned.

The specimens were all homogeniously heat treated by Materials Engineering Associates (MEA) per SRL instructions to produce a sensitized microstructure. This heat treatment was initially based on degree of sensitization measurements conducted by SRL using the Electrochemical Potentiokinetic Reactivation (EPR) method³. Using the EPR method, specimens of a cracked pipe from the P-reactor were determined to be sensitized to a level of about 11 C/cm² in the weld heat affected zone (HAZ). A heat treatment study was then performed by SRL on available material from R-reactor pipe, where, a treatment of 600°C/15-hours produced an EPR value of about 11 C/cm². Consequently, the bulk of the CERT specimens were heat treated at 600°C/15-hours (cooled at a rate of 44-56°C per hour) by MEA to produce a simulated "weld sensitized"

condition. In addition, six specimens were given a "furnace sensitized" condition (more severe) of 600°C/24-hours (cooled as above), to be used in the Option 1 screening tests (discussed later).

A random EPR check of CERT specimens at GE revealed that the simulated weld degree of sensitization was higher than determined by SRL (21-26 C/cm² compared to 11-C/cm²). The difference was due to a temperature effect, where SRL conducted their EPR tests at 25°C, and the GE tests were conducted at 30°C (higher temperatures causes higher EPR values). Regardless, since the SRL measurement technique was consistent between the actual pipe HAZ and the heat treated specimens, and since the CERT testing was basically a screening type study, it was mutually agreed that re-heat treatment of these relatively thin (0.1-inch), flat specimens (warpage concern) was not warranted. Photomicrographs in Figure 3-3 show the typical sensitized microstructures in the weld simulated and in furnace sensitized specimens.

3.2 CERT Test

The CERT test consists of conducting a relatively slow (1.2 mil/hour) "cross head speed" tensile test in the environment of concern. Details of this test have been presented earlier². In the present tests, the specimens were contained in 1-liter, stainless steel autoclave assemblies with the SRP environments continuously flowing past the specimen surface. The loads were applied by a unique sliding seal assembly connected to Instron tensile test machines which were modified specifically for CERT

testing. The facility consisted of five-Instron Model 1131 machines, and one-Instron Model 1125 machine (Figure 3-4).

The 1.2 mil/hour extension rate was selected based on a large body of data from tests performed by GE on both irradiated and non-irradiated material^{2,4}. This rate has consistently produced IGSCC in susceptible material in a reasonable test duration (1-2 weeks). The CERT loads, duration and temperatures were monitored continuously using a Keithley data acquisition system and an IBM PC computer. These data were then available for analysis and plotting against any of the environmental variables.

3.3 SRP Environment Simulation

3.3.1 Water Circulation Loops

It was necessary to design and construct special water/ environmental circulation loops to provide the complex SRP test environments to the CERT specimens on a refreshed basis. There were three of these water circulation loop modules constructed for the CERT tests (Figures 3-4 and 3-5). Each module was connected in a parallel fashion to a pair of CERT test frames. In this way it was possible to conduct duplicate tests in the same environment. A CERT test loop schematic is shown in Figure 3-6. The test system basically consists of three components: (1) a make-up/feedwater/clean-up circulating loop; (2) a chemical injection system; and, (3) a high-flow test loop.

In the make-up/feedwater portion of the system, the water is circulated at 200 cc/min through a regenerative heat exchanger, past a number of control instruments and sensors, and through clean-up demineralizers and oxygen removal cartridges before returning to the stainless steel make-up tank. The SRP gaseous variables (O_2 & CO_2) are blended with argon and sparged into the make-up tank. Circulation is achieved with a Milton Roy positive displacement diaphragm pump. This loop contains sensors to continuously monitor the dissolved oxygen concentration, pH, conductivity, and temperature. All of the signals from these sensors are connected to their respective signal conditioning instruments, and then to the Data Acquisition System and computer.

The chemical injection system consists of individual polyethylene tanks into which the desired chemicals are added based on calculated concentrations. The exact concentrations are then achieved by controlling the injection rate of each tank into the main loop stream using Fluid Metering, Inc. chemical injection pumps. A larger polyethylene refresh tank is used to replenish the water in the injection tanks when their level drops below one-third full. The water supply to this refresh tank comes from a deionized process line, and from any overflow in the make-up tank (to maintain volume balance). The overflow water is deoxygenated, but does contain carbon dioxide from the test loop. This CO_2 is removed by continuous argon sparging of the refresh tank, and argon overpressures in the injection tanks. During normal operation, very little make-up tank overflow water is needed, however, since sample water (discussed later) is also continuously being removed from the test loop.

In the test loop, the flow is boosted to 2 GPM using a March magnetic drive impeller pump. The water is cooled slightly and then trim heated to the desired test temperature using sealed, in-line heaters. The test water passes through one or both CERT vessels in a parallel mode, and also through an ECP vessel before returning to the booster pump. To maintain volume balance, a portion of the water is recirculated into the test loop, while the remaining portion is returned to the make-up water main loop through the primary system regenerative heat exchanger.

3.3.2 Chemical Analyses

The chemical composition of the test loops are determined on a real-time basis using an analysis system constructed for this program (Figure 3-7). The chemical analysis module consists of a Dionex ion chromatography system, an IBM hydrogen peroxide analyzer, and a Dohrmann carbon dioxide analyzer/Horiba infrared system. The console contains a pneumatic-activated 10-position sample valve which permits sampling three locations from each of three loops, and a 10th port is used to introduce standards into the analytical systems.

Each loop is plumbed to sample the make-up tank (feedwater), the influent to the test loops, and the effluent from the test loops. Continuous sampling of all three locations for each loop resulted in excessive water consumption which required frequent refilling and considerable test perturbation. Consequently, for normal test operation, only the effluent (test water sample WC #3 in Figure 3-6) was sampled continuously; the other

two samples were taken when needed to better understand loop operation.

The chemical analysis module is an automated sampling system which is driven by a menu-controlled IBM PC connected to a Keithley data acquisition system, shown schematically in Figure 3-8. Also shown schematically in Figure 3-9, is the subsystem configurations of the three components of the module. These three components are discussed separately below.

3.3.2.1 Anion Dionex Ion Chromatography System

The anion chromatography system measures the concentration of chloride, nitrate and sulphate by conductivity. A sodium carbonate/bicarbonate eluent is used as a mobile phase to carry the sample through an ion exchange column. The column is packed with a resin that contains many positively charged sites. The negative charged anions are attracted to the positive sites. Specific ion affinity for the ion exchange column affords separation of the anions. The eluent conductivity is chemically suppressed and the resulting acid from anions are measured using conductivity.

(1) Normal Flow

(2) When Sampling

The concentrator is loaded with a sample for ~200 sec. Then the eluent pushes the sample through the rest of the system (after loading, the injection valve is switched back to position (1)).

3.3.2.2 Hydrogen Peroxide Analyzer

The H_2O_2 concentration is measured by reacting H_2O_2 with iodide to produce iodine (I_2).

The iodine is then reduced to iodide and a current is generated.

The amperometric cell measures the current which is directly proportional to the concentration of I_2 .

The coulometric cell provides a built in calibration technique in which a

fixed current is passed through the cell. Iodide is then oxidized to iodine.

3.3.2.3 Carbon Dioxide Analyzer

A sample containing combined carbon dioxide is injected into a constant volume reactor containing dilute sulfuric acid. The H_2SO_4 reagent is continuously pumped into the reactor (excess volume being pumped to waste) and the reactor is continuously sparged with Nitrogen gas. The gas flows in the bottom and out the top to a nondispersive infrared detector. When the sample is injected into the reactor any carbonates that are present react with the acid and produce CO_2 . The CO_2 is sparged from the liquid and carried to the IR detector in the gas stream. Infrared radiation is emitted from a light source and passed through the sample and reference cells. Molecules absorb infrared radiation of a specific wavelength and the degree of absorption is proportional to the concentration at constant pressure. Therefore, if part of the infrared radiation is absorbed by the sample gas then a decrease in the amount of radiation reaching the detector will result. This difference causes a membrane between the sample and reference cells in the detector to produce electrical output which is amplified and directed to a meter.

The analytical equipment was designed to measure the variable concentrations over a fairly wide range (Table 3-2). This requirement was

accomplished by running standards at various ends of the range, dependent on the particular test specification. The PC menu can be changed to vary the sample time, but for the bulk of the testing each loop was sampled about once every two hours. A typical chromatogram displaying the data printed out after every analysis is shown in Figure 3-10. Typical trendgraphs which can be retrieved from the PC menu at any time are shown in Figures 3-11 through 3-14 for nitrate, sulphate, chloride, CO_2 and H_2O_2 .

3.4 Electrochemical Potential (ECP) Measurements

All three CERT loops were continuously monitored for ECP using vessels connected in series with the return water from the test vessels. The ECP's were measured for three reasons: 1) to establish potential values for IGSCC and to compare these values with measurements at SRL; 2) to provide data which is helpful in explaining unusual corrosion behavior; and, 3) ECP is generally a rapid indicator of loop transients. The ECPs were measured using electrodes connected to a Keithley data acquisition system and then to an IBM-PC. A Keithley switching/scanning instrument was also used to allow switching from electrode pairs, and between loops in a sequential mode. An ECP measurement was obtained on an electrode pair every hour. Each vessel contained four electrodes. These included two silver/silver chloride reference electrodes (GE high temperature types), a stainless steel metal electrode, and a platinum metal electrode. A schematic of the reference and metal-tipped electrodes is shown in Figure 3-15. The Type-304 stainless steel electrode was fabricated from a piece of SRP piping (pipe 5, side B), and was about 0.250-inch in diameter x 0.5-inch

long. The platinum electrode was machined to the same dimensions.

In addition to obtaining ECP measurements between the metal and the reference electrodes, measurements were also obtained between the vessel wall and the reference electrode, and between the two reference electrodes to act as checks of reference electrode stability.

3.5 Post Test Specimen Examination

The fracture surfaces of all CERT tested specimens were examined by Scanning Electron Microscopy (SEM) using a Model ISI S3A instrument. The examination was conducted to determine the mode of fracture (IGSCC, TGSCC, ductile), the number of secondary cracks present, and to measure the percent of IGSCC, if any, on the fracture surface.

In addition, a few selected specimens were mounted to perform cross-section metallography. The specimens were polished and then etched using 10% Oxalic Acid (electrolytically) to reveal the microstructure and the presence of any intergranular cracking.

Table 3-1.

Chemical Composition of CERT Specimen Material (SRP Archive
16-inch Diameter Pipe - Ring 2A)

Reference: Materials Engineering Associates Presentation,
Table 1, Senior Panel Review, March 26-27, 1986,
Vol 1 Reactor Tank Integrity ("Green Book").

Element	Weight Percent
Carbon	0.079
Manganese	1.50
Silicon	0.34
Phosphorus	0.031
Sulphur	0.024
Nickel	9.65
Chromium	18.27
Molybdenum	0.45
Boron	0.002
Cobalt	0.13
Copper	0.42

Table 3-2.

Test Program Variable Concentration Measurement Range

<u>VARIABLE</u>	<u>LEVELS</u>
CL ⁻	1 ppb to 100 ppb
NO ₃ ⁻	1 ppb to 1000 ppbm
SO ₄ ⁻	1 ppb to 200 ppb
CO ₂	10 ppb to 2000 ppb
Hydrogen Peroxide	100 ppb to 10000 ppbm
Oxygen	10 ppb to 8000 ppb

Figure 3-1. Schematic of SRP Archive Pipe (Type 304-Sch. 40) Showing
Sectioning for Specimen Fabrication (Ring No. 2 - Side A)

CCM: 24 5-11

300

211A7874

334' 24 5000'

3-20C

Title

MODIFIED CORROSION
TENSILE SPECIMEN (FLAT)

FIRST MADE FOR METALLURGICAL DEVELOPMENT

MAT'L:

① TO BE SPECIFIED BY MET. DEV.

NOTES:

1. MAINTAIN SYMMETRY BETWEEN THE HOLES & CENTERLINE OF GAGE SECTION.
2. MAINTAIN STOCK IDENTITY ON FINISHED PIECE

* $\sqrt[32]{}$ ON ALL SIDES
OF 1.250 LONG
GAGE SECTION.

63/✓ ALL OTHER SURFACES.

UNLESS OTHERWISE SPECIFIED USE	APPLIED PRACTICES	SURFACES ✱✓	TOLERANCES ON MACHINE DIMENSIONS		
			FRACTIONS	DECIMALS	ANGLES
			+ - +	+ - +	+ - +

REVISIONS	PRINTS TO

TEST SPECIMEN USED
OR SRP CERT PROGRAM

FIGURE 3-2. TEST SPECIMEN USED FOR SRP CERT PROGRAM

55-12 JAN. 12 1973

APPROVAL

12

1 PO

VNC

11

211 A7874

CONT. ON PAGE

34 NC

77-303-P 10-20-61
PRINTED IN U.S.A.

CHK'D E. Mullen 1-16-72

a 2A95-WS

b 2A17-PS

Figure 3-5. Typical Sensitized Microstructures in the Simulated Weld and Furnace Sensitized CERT Specimens (400X, Oxalic Acid Etch).

Figure 3-5. View of Recirculation Module Constructed
for the SRP Corrosion Test Program

Figure 3-6 Schematic Diagram of the CERT Test Loop.

• DIONEX
 • ANION
 • ANALYZER

• SM H2O2
 • ANALYZER

HORIBA
 INFRA-RED
 GAS ANALYZER

DOHRMANN
 CARBON
 ANALYZER

AUTOMATED SAMPLING SYSTEM

Figure 3-8. Chemical Analysis Module
Automated Sampling System

Figure 3-9. Chemical Analysis Instrumentation Subsystem Configuration

PPB H2O2 IN SAMPLE 989.8179
 MEAN 1 200 250 SEC 1644.216 STD DEV 1-11.74958
 Sample Points: Test Water - Loop B Date and Time: 10-27-1986 15:52:50
 Data File: S:RD102786.DAY Run # 34

Conditions:

	LSI	CD
Sample Volume (ul)	1.0	10.0
Peak Threshold	1.00	1.00
Initial Peak Width	40	100
Detector Range	3.0	1.0

Peak Identification				Response Factors		Peak Parameters								
No.	Pr #	Ion	Conc. (ppb)	Slope	Intercept	Start		Mid		End		Area	Height	BL
						Time	Ht	Time	Ht	Time	Ht			
1	1	chloride	46.783	4.90E-02	0.00E+00	107	4.6	116	3786.5	130	2948.4	23039.9	3180.47	1
1	2	nitrate	0.000	0.00E+00	0.00E+00	135	1548.5	182	1844.8	203	1728.6	6672.0	204.46	1
1	3	nitrate	617.918	1.61E-01	0.00E+00	208	1717.2	235	14457.3	334	1938.4	633972.8	12764.88	1
1	4	sulfate	211.476	1.93E-01	0.00E+00	337	1309.6	378	5165.9	461	1821.2	159002.5	3455.47	1
2	1	CO2	982.336	1.93E-01	0.00E+00	36	3401.7	105	13581.4	262	3357.0	479877.8	10179.65	2
3	1	peroxide	989.818	6.02E-01	0.00E+00	0	0.0	0	0.0	0	0.0	0.0	0.00	0

Figure 3-10. Typical Chemical Analysis Chromatogram

Figure 3-11. Typical Trendgraph for Nitrate and Sulphate During an SRP CERT Test

Figure 3-12. Typical Trendgraph for Chloride During an SRP CERT Test

Figure 3-13. Typical Trendgraph for Carbon Dioxide During an SRP CERT Test

Figure 3-14. Typical Trendgraph for Hydrogen Peroxide During an SRP CERT Test

Reference and Metal Electrodes

Figure 3-15. Schematic of Reference and Working Electrodes Used for SRP CERT Test Program.

4.0 TEST CONDITIONS

4.1 Option 1

As stated previously, the primary purpose of the Option 1 CERT tests was to verify that IGSCC could be produced in sensitized Type-304 (SRP archive) in a nominal SRP environment at an extension rate of 1.2 mil/h. To assure success, it was originally intended to test six simulated weld sensitized (15 hours at 600°C) and six furnace sensitized (24 hours at 600°C) specimens, two each in three environments. These environments, designated low, nominal and high are given in Table 4-1. The simulated weld sensitized (WS) specimens were tested first, where, due to the extent of IGSCC which resulted, there were changes made in the remaining test matrix. Two of the furnace sensitized (FS) specimens were tested under nominal conditions to provide additional verification of the corrosivity of this environment. The other four FS specimens were tested to study temperature effects and the influence of the source of dissolved oxygen. To study temperature, one specimen was tested at 120°C under low conditions, and one specimen tested at 35°C under high conditions. For the dissolved oxygen effects, both FS specimens were tested at 78°C under nominal conditions. In one test, however, the concentration of dissolved oxygen resulting from decomposition of the H_2O_2 was measured; no additional oxygen was added to the environment. In the other test, there was no H_2O_2 added, but gaseous oxygen was added to the concentration measured from the previous test (decomposition concentration).

These last two H_2O_2 decomposition tests indicated a need for additional understanding before formulating the Task A matrix. Consequently, a number of loop chemistry studies were performed without conducting any CERT tests. In these special tests, the H_2O_2 concentration was varied between 960-5600 ppb, and the temperature between 35-120°C, no other chemicals or gases were added to the environment. The test was continued until the measured concentration of dissolved oxygen appeared stable (steady state H_2O_2 dissociation), and then the O_2 concentration was recorded. This data was then used to derive statistical variable levels for the Task A CERT tests.

4.2 Statistical Experiment Design: The Central Composite Design

The first step in planning the experiment design for a test program is identification of the mathematical model form anticipated to satisfactorily represent test results. This is judged in advance so that the experiment can be designed to efficiently estimate the unknowns in the model. The model allows "observed values" of a dependent variable, from testing, to be generalized to obtain "predicted values" at any combination of the independent variables, within the range of each tested. The model is also known as a "prediction equation" or a "response surface equation".

In the present work the dependent variable was to be some CERT parameter reflecting IGSCC susceptibility. The independent variables which SRP identified for evaluation were the six shown below. Each, except temperature, is a concentration.

Chloride
Temperature
Sulphate
Oxygen
Hydrogen Peroxide
Carbon Dioxide

It was anticipated that both oxygen and hydrogen peroxide would be significant variables, but, from the Option 1 testing, it was noted that oxygen was produced by dissociation of hydrogen peroxide. Thus, both oxygen and hydrogen peroxide could not be set independently to the combinations of levels which would be required in a single experiment design. Accordingly, it was planned to perform separate testing in oxygen and hydrogen peroxide environments. Five variables would be tested in each environment, but in the hydrogen peroxide environment the oxygen obtained by dissociation would also be measured. For the oxygen environment, a model, linear in coefficients on the terms shown in Table 4-2, was adopted for planning purposes. For the hydrogen peroxide environment, a model was adopted containing the terms shown in Table 4-3. In both of these tables, the first-degree terms provide for slope of Y (the dependent variable) over each X_i (independent variable); the two-factor interactions provide for response-surface twist, a different slope of Y over X_i depending on the value of X_j ; and the second-degree (quadratic) terms provide for curvature of Y over each X_i as part of a parabola. While these terms alone may not model the data perfectly, they will identify the major trends. And data were not taken at test conditions which would be required for evaluating a

more extensive model. Following analysis of the data, only terms whose coefficients found statistically significant will be retained. An experiment design in the "central composite" class best lends itself to independently estimating coefficients in the proposed oxygen and hydrogen peroxide models. This design class has two parts: a linear part and a quadratic part. Each is required for estimating coefficients on the terms so designated in Tables 4-2 and 4-3, although the final model will be based on analyzing data from both parts together. One feature of a central composite design is its adaptability; only terms found significant in the linear part need be run in the quadratic part. This is based on the assumption that it would be rare for the coefficient on a quadratic term to be significant if the coefficient on the linear term for that variable was not significant. This adaptive feature offered a potential savings in the number of tests.

Selection of the central composite class of designs, and in particular the one used for both the oxygen and hydrogen peroxide testing, was based on the following considerations:

1. The model form.
2. The total number of specimens available.
3. The desire to provide for replication so the data would have an internal estimate of variability between tests repeated at the same test condition, important in

testing the coefficient estimates for significance.

4. The desire to estimate coefficients independently and with the smallest error of estimate. These two properties are obtained simultaneously.
5. The desire to use the least squares criterion and the multiple linear regression method in estimating the coefficients.

Based on the above considerations it was decided to run the linear parts of both the oxygen and hydrogen peroxide designs as one-half fractional factorials of five variables at two levels, $(2^5 - 32)/2 = 16$ test conditions. The half-factorial design provides independent estimates of the coefficients of the linear terms designated in Tables 4-2 and 4-3. However, there is an inherent assumption related to the pattern of confounding of the coefficient estimates. This confounding pattern can be seen in Table 4-4 which shows all of the 32 possible terms required to exactly define results from five variables tested at two levels. There are six groups of terms, designated A to F, namely, one constant, five first degree terms, ten two-factor interactions, ten three-factor interactions, five four-factor interactions and one five-factor interaction. In 32 tests (a full factorial), coefficients for all these terms could be estimated. However it is common experience that coefficients on the higher-order interaction terms (groups D, E and F) are rarely significant and can be assumed negligible. This permits the confounding pattern of the half-factorial to be acceptable. In this pattern each coefficient in group

C is evaluated as the sum of the coefficient which applies to that term and a counterpart in term group D; each coefficient on a term in group B is evaluated as the sum of itself and a counterpart in term group E; and term group A is evaluated as the sum of itself and the coefficient on the term in group F. By assuming negligible coefficients on terms in groups D, E and F, the coefficients estimated for terms in groups A, B and C are undistorted. Under this assumption the advantage of using half the number of test conditions, 16 instead of 32, can be realized and still provide a useful model. The test conditions for the linear part are given in Table 4-5. Five variables are tested in both oxygen and hydrogen peroxide linear designs; the test condition numbers for each are designated "O" and "P" before the number. The test conditions are given as combinations of coded levels of -1 and +1, called "corner" points. The need for the coded scale and the relationship of the coded scale to the physical scale for each variable is described below. Test conditions for the quadratic part are given in Table 4-6. They involve the "center" point (all variables at their 0 levels) and one-at-a-time testing at "star" points (+1.6 and -1.6) for each variable in turn, the other variables at their 0 levels. Following the linear design tests, different groups of three variables were selected for testing in the oxygen and hydrogen peroxide quadratic designs as indicated by "O" and "P" at the beginning of the test condition numbers in Table 4-6. The choice of the 1.6 level in the quadratic designs, and one replicate in the linear designs and two replicates at all test conditions in the quadratic designs was determined to provide acceptable independence of coefficient estimates for testing five variables in the linear designs and five, four or three variables in the quadratic designs. Rotatability,

the property of having the same prediction variance at a chosen radius in any direction from the centroid of data, was also acceptable.

The total number of specimens to be tested is summarized as follows:

<u>Design</u>	<u>Number of Variables</u>	<u>Number of Replicates</u>	<u>Number of Specimens</u>
Oxygen linear	5	1	16
Oxygen quadratic	3	2	14
Peroxide linear	5	1	16
Peroxide quadratic	3	2	14
		Total	60

Thus, 60 specimens were committed to this design, and it was assumed that three variables would be found significant for testing in the quadratic parts of the oxygen and hydrogen peroxide designs.

A symmetric coded scale for each variable provides for the desired independence of coefficient estimates and facilitates numerical interpretation. However, the physical scale for each variable does not involve equal intervals from minimum to nominal and from nominal to maximum values to be tested. To relate physical and coded scales, an exponential transform was used for each variable except temperature. A different exponent was required for each variable, obtained as follows. The coded level -1.6 for each variable was set equal to the transformed minimum

physical value, and coded level +1.6 was set equal to the transformed maximum physical value to be tested. The exponent chosen permitted level 0 on the coded scale to be set equal to the transform of the nominal value. With these transforms selected, physical values to be associated with the coded levels -1 and +1 were calculated. For each variable, the physical value associated with each coded scale value is shown in Table 4-7. The table also shows the tolerance within which it was planned to control the measured physical value of each variable, and it shows the exponent for the transform of each variable. The general forms of the transform equation are shown in Figure 4-1. They are given as both the coded scale value in terms of a physical scale value, and vice versa. The numerical relationship between the two scales for each variable is illustrated in Figure 4-2. This transform procedure advantageously accommodated the large differences in magnitude between minimum, nominal and maximum physical values to be tested (for example, 2, 30, 100 ppb chloride). For the temperature scale, the range was not great (40°C - 120°C) and an exponential transform was not used; the coded level 0 was set equal to 80°C .

Variables were assigned to columns in Tables 4-5 and 4-6 as shown. The actual sequences for running the test conditions, their assignment to one of three or four loops available, and selection of test specimens for them were all arranged in a random manner.

Thus, the following test and analysis plan was established:

1. The oxygen linear design would be run first.
2. The results of the oxygen linear design would be analyzed and the significant variables identified for testing in the oxygen quadratic design.
3. The oxygen quadratic design would then be run.
4. By analyzing the results of both the oxygen linear and quadratic designs, the variables in the combined linear and quadratic model having significant coefficients would be identified and their coefficients estimated.
5. The hydrogen peroxide linear design would then be run; the oxygen produced by dissociation would be measured and recorded.
6. For each hydrogen peroxide linear test condition, the value of the dependent variable predicted by the oxygen model would be calculated.
- * 7. The difference of the observed values from the predicted values in the hydrogen peroxide linear design would be obtained.
- * 8. By analyzing these differences, the terms in an incremental hydrogen peroxide model having significant coefficients

would be identified.

9. Steps 5, 6 and 7 would be repeated for the hydrogen peroxide quadratic design.

* 10. Linear and quadratic differences would be analyzed to produce a combined hydrogen peroxide incremental model.

* 11. The final hydrogen peroxide model would consist of the oxygen model plus the incremental hydrogen peroxide model.

* When the data were analyzed, it was found that this difference method was not needed; oxygen was not an important variable in its own model (nor in the hydrogen peroxide model). Accordingly, the adopted hydrogen peroxide model was developed from only the hydrogen peroxide data.

4.3 Low Chloride-Sulphate Test Extension

Based on the results of testing in the hydrogen peroxide environment under the central composite design, it was deemed important to test whether there would be an advantage in that environment of having combinations of lower levels of chloride and sulphate than those tested. Accordingly, four additional tests with single replicates were carried out at the test conditions in Table 4-8.

4.4 Shield Water Environment

Six additional CERT tests were performed to assess the IGSCC of sensitized Type-304 stainless steel in simulated SRL shield water environments. These environments included high chloride (250 ppb) or high sulphate (2000 ppb) in a hydrogen peroxide design at 80°C, the other variables at their nominal levels, and two tests in very high nitrate (3000 ppb) but with the pH maintained at 4.9-5.3, and all other test variables at their nominal levels. Two specimens were tested in each of the three environments.

Table 4-1. Environmental Variable Levels for Option 1 CERT Tests

Environmental Variable	Variable Level (ppb)		
	Low	Nominal	High
Oxygen	80-100	900-1100	7200-8800
Hydrogen Peroxide	300-500	1800-2200	4500-5500
Carbon Dioxide	15-30	270-330	900-1100
Chloride	1-3	24-36	85-115
Sulphate	2-6	40-60	450-550
pH	4.9-5.3	4.9-5.3	4.9-5.3
Nitrate	316-793	316-793	316-793
Temperature (°C)	33-37	95-105	115-125

<u>Term</u>	<u>Part of design required to estimate coefficient (1)</u>
C, T, S, X, D,	linear
<u>C</u> ² , <u>T</u> ² , <u>S</u> ² , <u>X</u> ² , D ² ,	quadratic (2)
CT, CS, CX, CD,	linear
TS, TX, TD,	linear
SX, SD,	linear
XD and	linear
the intercept	both

where C = chloride concentration, ppb

T = temperature, °C

S = sulphate concentration, ppb

X = oxygen concentration, ppb

D = carbon dioxide concentration, ppb

Notes: (1) Coefficients and the intercept in the final model are estimated by fitting data from both linear and quadratic parts of the design simultaneously.

(2) The quadratic design selected provided for estimating coefficients on only the three terms underscored; they were the only quadratic terms offered for fitting.

Table 4-2. Terms whose Coefficients can be Estimated, Oxygen Designs

<u>Term (1)</u>	<u>Part of design required to estimate coefficient (2)</u>
C, T, S, P, D,	linear
<u>C</u> ² , <u>T</u> ² , <u>S</u> ² , <u>P</u> ² , <u>D</u> ² ,	quadratic (3)
CT, CS, CP, CD,	linear
TS, TP, TD,	linear
SP, SD,	linear
PD and	linear
the intercept	both

where C = chloride concentration, ppb

T = temperature, °C

S = sulphate concentration, ppb

P = peroxide concentration, ppb

D = carbon dioxide concentration, ppb

- Notes: (1) It is assumed that the concentration of oxygen by dissociation will be sufficiently correlated with the peroxide concentration that no significant additional effect can be estimated. This is checked.
- (2) Coefficients and the intercept in the final model are estimated by fitting data from both linear and quadratic parts of the design simultaneously.
- (3) The quadratic design selected provided for estimating coefficients on only the three terms underscored; they were the only quadratic terms offered for fitting.

Table 4-3. Terms whose Coefficients can be Estimated, Hydrogen Peroxide Designs

<u>Term Group</u>	<u>Form of Term</u>	<u>Number of such Terms for Five Variables</u>
A	Intercept	1 constant
B	X_i	5 1st degree terms
C	$X_i X_j$	10 2-factor interactions
D	$X_k X_l X_m$	10 3-factor interactions
E	$X_j X_k X_l X_m$	5 4-factor interactions
F	$X_i X_j X_k X_l X_m$	1 5-factor interaction
		<hr/> 32 total number of terms

Table 4-4. Pattern of Confounding of Coefficient Estimates in the Linear Parts of the Designs

Test Condition Number	Variable				
	CLC	TEMPC	SO4C	OXC or PEROXC	CO2C
	Level on Coded Scale				
01 P1	-1.	-1.	-1.	-1.	-1.
02 P2	-1.	-1.	-1.	-1.	-1.
03 P3	-1.	-1.	-1.	-1.	-1.
04 P4	-1.	-1.	-1.	-1.	-1.
05 P5	-1.	-1.	-1.	-1.	-1.
06 P6	-1.	-1.	-1.	-1.	-1.
07 P7	-1.	-1.	-1.	-1.	-1.
08 P8	-1.	-1.	-1.	-1.	-1.
09 P9	-1.	-1.	-1.	-1.	-1.
010 P10	-1.	-1.	-1.	-1.	-1.
011 P11	-1.	-1.	-1.	-1.	-1.
012 P12	-1.	-1.	-1.	-1.	-1.
013 P13	-1.	-1.	-1.	-1.	-1.
014 P14	-1.	-1.	-1.	-1.	-1.
015 P15	-1.	-1.	-1.	-1.	-1.
016 P16	-1.	-1.	-1.	-1.	-1.

"Corner" Points

CLC = Chloride concentration, coded levels
 TEMPC = Temperature, coded levels
 SO4C = Sulphate concentration, coded levels
 OXC = Oxygen concentration, coded levels (oxygen design)
 PEROXC = Hydrogen peroxide concentration, coded levels (peroxide design)
 CO2C = Carbon dioxide concentration, coded levels

Test Condition Numbers designated "O" apply to the oxygen design, those designated "P" apply to the peroxide design.

For physical levels corresponding to these coded levels, see Table 4-7.

Table 4-5. Test Conditions for Oxygen and Peroxide Linear Designs,
 Coded Levels

Test Condition Number	Variable					
	CLC	TEMPC	SO4C	OXC or PEROXC	CO2C	
Level on Coded Scale						"Star" Points
— P17	1.6	0.	0.	0.	0.	
— P18	-1.6	0.	0.	0.	0.	
019 —	0.	1.6	0.	0.	0.	
020 —	0.	-1.6	0.	0.	0.	
021 P21	0.	0.	1.6	0.	0.	
022 P22	0.	0.	-1.6	0.	0.	
023 P23	0.	0.	0.	1.6	0.	
024 P24	0.	0.	0.	-1.6	0.	
— —	0.	0.	0.	0.	1.6	
— —	0.	0.	0.	0.	-1.6	
027 P27	0.	0.	0.	0.	0.	"Center" Point

CLC = Chloride concentration, coded levels
 TEMPC = Temperature, coded levels
 SO4C = Sulphate concentration, coded levels
 OXC = Oxygen concentration, coded levels (oxygen design)
 PEROXC = Hydrogen peroxide concentration, coded levels (peroxide design)
 CO2C = Carbon dioxide concentration, coded levels

Test Condition Numbers designated "O" apply to the oxygen design, those designated "P" apply to the peroxide design.

For physical levels corresponding to these coded levels, see Table 4-7.

Table 4-6. Test Conditions for Oxygen and Peroxide Quadratic Designs,
Coded Levels

CODED LEVEL	CHLORIDE, CL, ppb	TEMPERATURE, TEMP, °C	SULPHATE, SO4, ppb	OXYGEN, OX, ppb	HYDROGEN PEROXIDE, PEROX, ppb	CARBON DIOXIDE, CO2, ppb
-1.6	2 ± 1	40 ± 2	10 ± 2	100 ± 20	400 ± 100	20 ± 5
-1.0	8.2 ± 2	55 ± 2	17 ± 5	244 ± 40	845 ± 125	82 ± 10
0	30 ± 6	80 ± 3	50 ± 10	1000 ± 100	2000 ± 200	300 ± 30
1.0	68 ± 8	105 ± 5	187 ± 30	3755 ± 400	3703 ± 350	683 ± 70
1.6	100 ± 15	120 ± 5	500 ± 50	8000 ± 800	5000 ± 500	1000 ± 100
NOMINAL	30 ± 6	100 ± 5	50 ± 10	1000 ± 100	2000 ± 200	300 ± 30
Exponent	0.43815	*	-0.18508	0.046565	0.45812	0.43815

* Linear scale, no exponent required

For use of exponents, see Figure 4-1.

Table 4-7. Physical Levels Related to Coded Levels, Oxygen and Peroxide Designs

Test Condition Number	Chloride Concentration		Sulphate Concentration	
	CLC, Coded Level	CL, Physical Level, ppb	SO4C, Coded Level	SO4, Physical Level, ppb
P48	-1.6	2	-1	17
P50	$-(1/3)1.6 = -0.533$	16.5	-2	7.2
P51	$-(2/3)1.6 = -1.067$	7.4	-2	7.2
P52	-1.6	2	-2	7.2

Temperature was tested at the +1 level, and Peroxide and CO₂ were tested at the 0 level on the coded scale.

Table 4-8. Test Conditions for Low Chloride-Sulphate Test Extension,
Peroxide Environment

The exponents, $\exp$, in Table 4-7 were calculated so that $X^{\exp}$, where X is a physical value of a variable, is proportional to a particular coded scale, XC , and X = stated minimum, nominal and maximum values, which are not equally spaced, correspond to $XC = -1.6, 0$ and $+1.6$ which are. Inherent in the evaluation of each $\exp$ is an equation relating X and XC . Both XC in terms of X and X in terms of XC are illustrated below using the above diagram where the diagonal line reflects the proportionality of $X^{\exp}$ to XC . XCS , the coded value corresponding to a selected physical value, XS , will be derived first.

In the diagram, the horizontal scale is the coded scale, XC ; its range from 0 to +1 is used. The vertical scale is $X^{\exp}$. The values of $X^{\exp}$ at $XC = 0$ and at $XC = +1$ are known; $XS^{\exp}$ at XCS is also known. As illustrated in the diagram, by proportionality,

$$\frac{h_s}{h} = \frac{v_s}{v}. \text{ Since } h_s = XCS - 0 = XCS \text{ and } h = 1 - 0 = 1, \frac{h_s}{h} = \frac{XCS}{1} = XCS. \text{ Also,}$$

$$v_s = (XS^{\exp} \text{ at } XCS) - (X^{\exp} \text{ at } 0), \text{ and } v = (X^{\exp} \text{ at } 1) - (X^{\exp} \text{ at } 0).$$

Since $XCS = \frac{h_s}{h} = \frac{v_s}{v}$, XC in terms of X , as XCS in terms of XS , is

$$XCS = \frac{(XS^{\exp} \text{ at } XCS) - (X^{\exp} \text{ at } 0)}{(X^{\exp} \text{ at } 1) - (X^{\exp} \text{ at } 0)}.$$

X in terms of XC , as XS for a selected XCS , is found by first solving for $(XS^{\exp} \text{ at } XCS)$ by

$$(XS^{\exp} \text{ at } XCS) = XCS((X^{\exp} \text{ at } 1) - (X^{\exp} \text{ at } 0)) + (X^{\exp} \text{ at } 0), \text{ from which}$$

$$XS \text{ at } XCS = (XS^{\exp} \text{ at } XCS)^{1/\exp}.$$

Figure 4-1. Transform Equations

Figure 4-2. Relationships Between Physical and Coded Scales

5.0 TEST RESULTS AND DISCUSSION

5.1 Option 1

5.1.1 CERT Tests

The results of the Option 1 CERT test results are given in Table 5-1, and shown graphically in Figure 5-1. It is apparent from these data that both temperature and environment have a strong effect on IGSCC. At 35°C, there was no stress corrosion cracking noted in specimens tested in either the low or high variable level environment. However, at 120°C, cracking was severe in both the low and high environments (89 and 100% IGSCC, respectively), but the failure times and ductilities revealed improvement in the low environment.

In the nominal environment (Figure 5-1), there was a slight degradation in properties when specimens were tested at 100°C compared to 78°C, but a significant improvement was observed at 78°C when the H₂O₂ was removed from the environment.

The appearance of the weld sensitized specimens after CERT testing in the high and low variable level environments are shown in Figure 5-2, while typical fracture surfaces are shown in Figures 5-3 and 5-4, respectively. A metallographic section is shown in Figure 5-5 for specimens tested at 120°C in the high and low environment, where, the extent of IGSCC is clearly evident.

Finally, an example of the load-time curves for a few of the Option 1 CERT specimens is shown in Figure 5-6. Here, the deleterious effects of higher temperature and higher concentrations of chemical variables is reflected in shorter failure times and lower maximum loads to fracture during the CERT test.

5.1.2 ECP

The ECPs measured during the Option 1 CERT tests are listed as Footnote (b) in Table 5-1. There was greater than 100mV difference between the low and nominal or high levels of variables, however, the high levels were lower (less positive) than the nominal levels. These values were measured for the weld sensitized specimen tests, and indicate a loop dependence (which persisted even throughout the Task A tests which are discussed later). However, based on studies⁵ performed on sensitized Type-304 stainless steel in BWR environments, all of these potentials are well within the regime where IGSCC is expected.

An example of the rapid response in measured ECP is shown for Loop C in Figure 5-7, where the level of HNO_3 was increased to study test sensitivity. The ECP was also very sensitive to the addition of H_2O_2 to the test environment, as shown for Loop B in Figure 5-8.

5.1.3 Hydrogen Peroxide/Oxygen/Temperature Study

An overview of the results of the hydrogen peroxide/oxygen/temperature

study is displayed in Figure 5-9. It is apparent that the H_2O_2 dissociation varied between test facilities, and between Loops within a facility. These data (variations) were used to formulate the experimental design for CERT and crack growth testing for the SRP corrosion program.

5.2 CERT Results from Central Composite Design, Low Chloride-Sulphate Test Extension, and Shield Water Environment Tests.

5.2.1 Central Composite Design

The CERT test results are presented in tabular form in this section, and will be presented in a statistical format in Section 5.3. These results will then be discussed in a summary fashion in Section 6.1.

The CERT test results for the Linear Oxygen and Hydrogen Peroxide Designs are given in Tables 5-2 and 5-3, and for the Quadratic Oxygen and Hydrogen Peroxide Designs in Tables 5-4 and 5-5, respectively. An example of all of the data acquired for a single CERT test specimen is given in Appendix A, and data plots showing actual chemical analyses within the tolerance limits for all of the main variables are shown in Appendix B.

5.2.2 Low Chloride - Sulphate Test Extension

The results of CERT testing additional specimens to further study the effects of low levels of chloride and sulphate are given in Table 5-6.

5.2.3 Shield Water Environment

The results from CERT tests to study the IGSCC of Type 304 stainless steel in simulated SRP shield water environments are given in Table 5-7.

5.2.4 Electrochemical Potential (ECP)

The range of ECP's measured by GE during the numerous CERT tests are shown in Figure 5-10 compared to the range measured at a Savannah River reactor by SRL. In the presence of H_2O_2 (SRL reactor contains ~2000 ppb H_2O_2), there is excellent agreement between actual reactor ECPs and GE laboratory data. In the absence of H_2O_2 , the GE laboratory ECPs are shifted about 200 mV more negative. These data reveal the oxidizing power of the H_2O_2 , and suggest that H_2O_2 would promote IGSCC by driving the potential in the positive direction. Although this is probably the case, the ECPs for the non- H_2O_2 environments are still quite positive, and, based on BWR technology at higher temperatures, are still presumably well within a stress corrosion cracking regime.

The average of ECP's measured during the Oxygen/Hydrogen Peroxide/Temperature studies are presented in Figure 5-11. Again, the influence of H_2O_2 in shifting the potentials in a more positive direction is apparent. The difference in temperature dependencies (slopes) shown by the curves in Figure 5-11 is probably due to data scatter, where, at these low temperatures the ECP response of stainless steel is generally quite sluggish.

5.3 Statistical Analysis of Results

5.3.1 Introduction

The analytical objective is to define two prediction equations for IGSCC, one in the oxygen environment and the other in the hydrogen peroxide environment. The equations predict a dependent variable related to IGSCC in terms of independent variables which characterize the environment. The test data are analyzed so that each term from those listed in Tables 4-2 and 4-3 which are important in explaining the pattern of the data are retained. Thus each equation will contain essential terms and be free of superfluous terms. Statistically, terms will be selected on the basis that the difference between the coefficient estimate and zero for each term is "significant at the 10% level". This level of significance is typically used in engineering tests and means that the coefficient estimate has a 10% chance of being found significant when it is not really different from a true value of zero (null hypothesis). Thus, a term is retained only if there is little chance that the true value of its coefficient could be zero. A term whose true coefficient is zero has no effect on the prediction.

The first step in the analysis was to decide on what parameter from the CERT testing would most consistently reflect IGSCC. In general, long failure times of a specimen in a CERT test indicate that little IGSCC occurred so. Such failures generally show ductile behavior. Conversely, short failure times are accompanied by fracture surfaces which are not

ductile, but are primarily IGSCC. Thus, candidate CERT results related to IGSCC include time to failure and the ductility measures of elongation and reduction of area. Failure in some specimens occurred at specimen shoulder or tab-end locations rather than in the gauge section, so time to maximum stress and the maximum stress value achieved during the test were also considered. Rather than trying to reconcile a number of prediction equations, one for each possible parameter, it was decided to chose a single parameter which reflected the influence of a number of individual ones. Using this approach some averaging occurred and the chosen parameter represented a more consistent measure of IGSCC than any single parameter might have.

Time to maximum stress was chosen as the basic parameter. This was preferred over time to failure because some shoulder or tab-end failure times exceeded their respective times to maximum stress in an unrepresentative manner. Also, other work in which CERT tests were interrupted showed IGSCC initiation at a time close to the maximum load. Selection between a linear time scale and a log time scale was made using the following rationale. It is typical that both effects on and variabilities of event times related to failure tend to be proportional to the predicted value rather than a fixed value. That is, under a set of conditions where the predicted value of dependent variable Y is 10 hours, the effect on Y of a certain change in independent variable X might be +1 hour, for example, whereas under another set of conditions where the predicted value is 100 hours the same effect would be +10 hours. Moreover, variability of data at 10 hours might have a standard deviation of 1 hour,

whereas at 100 hours the standard deviation would more likely be 10 hours. Such effects and variabilities become the same at 10 and 100 hours when a log time scale is used for Y. Having equal variability of data over all test conditions is also an assumption in the curve fitting process. Accordingly, the log time to maximum stress scale was used, designated LTMS.

A procedure was devised to permit both the ductility and the maximum stress value to influence the LTMS value. For "ductility", the sum of the percent elongation and percent reduction of area was obtained. The summed ductility values for each test in the oxygen and hydrogen peroxide designs (linear and quadratic) are plotted relative to their LTMS values in Figure 5-12. The best fit was drawn manually; a line normal to the curve was drawn from each point and its intersection value on the curve was taken as the LTMS adjusted for ductility. Similarly, the plot of maximum stress values versus LTMS values appears in Figure 5-13. The same adjustment process was used for maximum stress. The two adjusted LTMS values were averaged to produce a final value designated log adjusted time to maximum stress, LATMS. The relationship of log time to failure to LATMS values is shown in Figure 5-14. It can be seen that these two measures are fairly closely related, with some of the shoulder or tab-end failures furthest from the curve. The LATMS values were adopted for use in the statistical analyses.

In the following subsections, the test results are tabulated so as to relate directly to the statistical analyses. In Tables 5-8 through 5-13

the following information is given. Individual specimens are identified by a reference number and their test condition number in addition to their 2A number; the test loop (A, B, C or D) used and the sequence of the test in the loop are identified; test conditions on the coded scale are given; CERT parameters time to fail (TTF), time to maximum stress (TMS), average time to maximum stress (ATMS), log average time to maximum stress (LATMS), maximum stress and ductility measures elongation and reduction of area are given; and finally, the ECP of the Type 304 stainless steel is included (ECP-SS). For each hydrogen peroxide design test, the level of observed oxygen from dissociation is given and for Option 1 tests, the heat treatment, oxygen or hydrogen peroxide environment, and level and source of observed oxygen are also given.

5.3.2 Analysis of the Oxygen Design Results

5.3.2.1 Oxygen Model Derivation

The oxygen linear design results given in Table 5-8 were analyzed first, to identify significant variables for subsequent testing in the quadratic design. With LATMS as the dependent variable, multiple linear regression analysis was performed on the data from the 16 tests. The coded scale was used for each dependent variable. The nominal coded levels were used since the average actual coded levels differed little from the nominal values. All linear terms listed in Table 4-2 were offered for fitting. This fitting was done in two groups so that the number of test data exceeded the number of coefficients being estimated by at least two degrees of freedom.

Terms were dropped until the coefficients on all terms remaining were significant at the 10% level as indicated by their F value's exceeding the critical F at the 90% point for the current degrees of freedom.

The results of the regression analysis are given in Table 5-14 (column 5-14A). The overall quality of fit is reflected in the R-squared value. R-squared is the square of the multiple correlation coefficient, sometimes called the "index of determination". The value is 0.954. The closer this value approaches 1.0 the better the model fits the data overall, so this fit for the oxygen linear design is very good. The terms whose coefficients were found significant in the oxygen linear model are also given in Table 5-14 (column 5-14A). Coefficients are significant because their F values exceed the critical F value (3.23) for 10% level of significance and the degrees of freedom involved (11). The higher a coefficient's F value is, the lower the chance is that the true coefficient is zero. It can be seen in Table 5-14 (column 5-14A) that the temperature term had by far the most significant coefficient, as indicated by the high F value of its coefficient. Also significant, however, were the coefficients on the terms for sulphate, the two-factor interaction between temperature and sulphate, and the two-factor interaction between temperature and carbon dioxide. Two coefficients are conspicuous by their absence. One is on the oxygen term. Thus, within the range of oxygen values tested (244 to 3755 ppb, -1 to +1 on the coded scale), the oxygen level made no significant difference in LATMS. The other is on the chloride term; in the oxygen environment, changing chloride from 8 to 68 ppb did not affect LATMS significantly.

From these results, three variables, temperature, sulphate and oxygen were chosen for testing in the quadratic part of the design. Temperature and sulphate have significant coefficients. Although the coefficient on oxygen was not significant it was selected in order to investigate its importance over a wider range (100 to 8000 ppb) in the quadratic part. Because their coefficients were not significant, chloride and carbon dioxide were not selected.

The quadratic testing was carried out at the seven test conditions designated O19-O24 and O27 in Table 4-6. With the exception of O20, two specimens (replicated pairs) were tested simultaneously at each test condition, taking advantage of the dual-autoclave configuration of each loop. Test condition O20, the -1.6 level of temperature, was not replicated because a fully ductile failure was anticipated, and was obtained. Test condition O27, the zero level "center" point was replicated three times to improve definition of this point, vital to estimating the coefficients on all of the quadratic terms.

The oxygen quadratic results are given in Table 5-9. The quadratic testing added 14 data points to make a total of 30 for the combined oxygen linear and quadratic analysis. All terms in Table 4-2, both linear and quadratic except as noted, were offered for fitting; terms whose coefficient estimates had nonsignificant F values were successively dropped, as described above for the oxygen linear analysis. The results of the regression analysis for the combined oxygen linear and quadratic design are given in Table 5-14 (column 5-14B). R-squared at 0.936 and standard

deviation of residuals at 0.113 indicate a quality of fit comparable to that for the oxygen linear design alone. As in the analysis of the linear design data, temperature is the dominating term followed again by sulphate, the temperature by sulphate interaction, and the temperature by carbon dioxide interaction; the coefficient on the quadratic term for sulphate is also significant. The last is due to curvature of the LATMS points over the sulphate scale. Importance of individual variables is discussed in section 5.3.2.3.

Using the coefficients from Table 5-14 (column 5-14B), the adopted prediction equation for the oxygen environment using variables on the coded scale, is given below.

Adopted Oxygen Model

$$\begin{aligned}
 \text{LATMS} = & 2.085 \\
 & -0.417 \times \text{TEMPC} \\
 & -0.0688 \times \text{SO4C} \\
 & -0.0651 \times \text{TEMPC} \times \text{SO4C} \\
 & -0.0598 \times \text{TEMPC} \times \text{CO2C} \\
 & +0.0583 \times (\text{SO4C})^2
 \end{aligned}
 \tag{5-1}$$

This prediction equation, using variables on the physical scale, is given below.

$$\text{LATMS} = 4.862$$

$$-0.02318 \times \text{TEMP}$$

$$-6.441 \times \text{SO4E}$$

$$+0.03621 \times \text{CO2E}$$

$$+0.02477 \times \text{TEMP} \times \text{SO4E}$$

$$-4.526 \times 10^{-4} \times \text{TEMP} \times \text{CO2E}$$

$$+5.274 \times (\text{SO4E})^2$$

(5-2)

For both Equations (5-1) and (5-2) the symbol for each variable is as follows:

	(5-1)	(5-2)	(5-2)
	Coded	Physical	Physical
	Scale	Scale	Values with
			Exponents
Log ₁₀ (Adjusted Time to Maximum Stress)	LATMS	LATMS, Log hours	----
Temperature	TEMPC	TEMP, °C	----
Sulphate Concentration	SO4C	SO4, ppb	SO4E
Carbon Dioxide Concentration	CO2C	CO2, ppb	CO2E

where $\text{SO4E} = \text{SO4}^{-0.18508}$ and $\text{CO2E} = \text{CO2}^{0.43815}$

The fact that more terms appear in Equation (5-2) than in (5-1) is a consequence of Equation (5-1)'s having interaction and quadratic terms, and of the origin of the scale for each variable being shifted in Equation (5-2) relative to Equation (5-1). It does not affect the validity of significance tests done on the coefficients in deriving Equation (5-1).

Two topics will be covered in the remainder of this section. In section 5.3.2.2 a description will be given of a figure on which the model and its relationship to observed values can be visualized. This is followed in section 5.3.2.3 by identification of regions in which the total slope of LATMS over each variable is significantly different from zero, indicating the conditions over which that variable is important in predicting LATMS. In order to accurately describe the properties of the Adopted Oxygen Model, it will be helpful to give a name to each part of the model, together with statistical properties of each part. This is done in Table 5-15.

5.3.2.2 Graphical Representation of the Adopted Oxygen Model

A graphical representation of the data points and the model is given in Figure 5-15. Symbol and line coding are given on sheet 2 of the figure. To facilitate interpretation, the pertinent features of Figure 5-15 will be described in the following order:

1. Identification of scales;
2. Location of data points;

3. Highlighting selected lines in the prediction surfaces calculated by the model, as fitted to the data points;
4. Highlighting each term in the model by its effect on the predicted values; and
5. Indicating how data points make coefficients on omitted terms non-significant.

In Figure 5-15 the vertical scale is the dependent variable log adjusted time to maximum stress, LATMS. This scale runs from 1.0 to 3.0, from 10 hours to 1000 hours. Since this is a log scale, an increment represents change by a factor; for reference, a factor of two change is shown by the scale to the left. Shorter times to maximum stress are associated with an increase in IGSCC. There are two horizontal scales for independent variables: chloride, marked CLC, and sulphate, marked SO4C. The coded scales are used for these variables; the physical values corresponding to the coded scale values entered on the figure are given in Table 4-7.

The 16 data points from the oxygen linear design are located as follows. The eight data points at the -1 temperature level, 55°C, are shown with the label TEMPC = -1; they are 01-02, 03-04, 09-010 and 011-012. These points are shown above the four corners at all combinations of -1 and +1 on the chloride and sulphate scales, according to their test conditions. Similarly, the eight data points from testing at the +1 temperature level, 105°C, are shown with the label TEMPC = +1; they are 05-06, 07-08, 013-014

and 015-016. The 14 data points from the oxygen quadratic design are shown by the inverted triangles. Data points 019 and 020 at the +1.6 and -1.6 temperature levels respectively (all other variables at 0 level) are located on the center stem. Data points 021 and 022 at +1.6 and -1.6 sulphate levels respectively are shown above the sulphate scale, at TEMPC = 0. The data at +1.6 and -1.6 oxygen levels, 023 and 024 respectively, are shown on the center stem, along with the center point data, 027.

Prediction surfaces related to the oxygen linear design test conditions are shown by solid and broken lines. At TEMPC = -1, predicted values along combinations of -1 and +1 on the chloride and sulphate scales and at the -1 level for CO₂ are shown by the four solid lines marked "CO₂C = -1". Similar predictions at the +1 CO₂ level are shown by the four broken lines; these are marked "CO₂C = +1". At the four corners of each surface are four small solid circles; these are the predicted values from the model for the respective test conditions. The symbol table identifies data points at the +1 CO₂ level and the -1 CO₂ level by open circles and open circles with a horizontal bar respectively. Data point 02 is predicted by the model as the small solid circle beneath it, and data point 01 by the solid circle beneath it. These predictions are in good agreement with observed values, and similarly, the six data points at the other three corners are predicted in reasonable agreement with observed values. Similar agreement of predicted to observed values is shown at the +1 temperature level. Predicted values related to the oxygen quadratic design test conditions at TEMPC = 0 are also shown by small solid circles. The dashed line identifies the prediction surface over the sulphate scale at TEMPC = 0 and

is curved downward in the center to accomodate the 023, 024 and 027 data.

How the terms in Equation (5-1) appear in Figure 5-15 is described as follows. The terms are taken in decreasing order of the F values of their coefficients as shown in Table 5-14 (column 5-14B). The large effect of temperature is clearly visible by the vertical separation of the surfaces. In particular, the predicted values of LATMS at TEMPC = -1.6, -1, 0, +1 and +1.6, all other variables at their zero level, are shown by small solid circles so labelled on the center stem. These cover a wide span of LATMS values, reflecting the large coefficient on the temperature term. IGSCC decreases with decreasing temperature. The smaller, but significant, effect of sulphate can be seen by the negative slope of the dashed line over sulphate at TEMPC = 0. This line is also curved, reflecting the sulphate squared term. Moreover, this slope changes from near 0 at TEMPC = -1 to more negative at TEMPC = +1, a consequence of the temperature by sulphate interaction. Thus, IGSCC decreases with decreasing sulphate level, more so at TEMPC = +1.

Although the coefficient on carbon dioxide was not significant, the significant coefficient on the term for interaction of carbon dioxide with temperature can be seen in Figure 5-15. At TEMPC = -1 (55°C) increased LATMS values are predicted at the +1 level of carbon dioxide (683 ppb) when compared with its -1 level (82 ppb). This describes the upper pair of surfaces. At TEMPC = +1 (105°C) this behavior is reversed; decreased LATMS values are predicted at the +1 level of carbon dioxide. This describes the lower pair of surfaces.

The nonsignificance of the coefficient on chloride can also be seen in Figure 5-15. All predicted values over the chloride scale are parallel to its axis. Thus, there is no effect of changes in chloride (from 8 to 68 ppb, -1 to +1 on the coded scale) in the oxygen environment. The chloride scale was included in Figure 5-15 because it will be useful in making comparisons to the hydrogen peroxide results.

Finally, the absence of an oxygen effect can be seen in Figure 5-15 by the lack of a consistent relationship between circles coded with diagonal lines and open circles, and by the lack of sufficient difference among the O23, O24 and O27 data points.

To provide a more complete analysis of the data, in the oxygen linear and quadratic analysis not only were the terms of the test variables in Table 4-2 offered for fitting but also "indicator" variables to distinguish a different intercept for Loops B, C and D relative to Loop A. The ECP-SS value of the stainless steel electrode was also offered for fitting. Coefficient estimates on neither any of these indicator variables nor ECP-SS proved to be significant. Thus, in the oxygen environment, there was no bias of results assignable to the particular loop in which the testing was done, and the ECP-SS values added no new information.

5.3.2.3 Importance of Individual Variables in the Adopted Oxygen Model

The adopted oxygen model can be used to identify which physical variables in the oxygen environment are important in determining IGSCC of Type 304

stainless steel. A variable is important if a change in its level causes a statistically significant change in IGSCC, as measured in this work by LATMS. Importance of variables will be discussed first in general terms and then for the Adopted Oxygen Model specifically.

A variable, X_i , will be designated "important" if the "total slope" of LATMS over that variable is found to be significant at the 10% level.

$$\text{Total slope of LATMS over } X_i = \partial \text{LATMS} / \partial X_i \quad (5-3)$$

How the test of significance for total slope is carried out will now be described, giving examples for terms of different forms. First a definition: the "order" of an equation is that of the term having the highest number of X's in a product. The term X_i is first order, X_i^2 or $X_i X_j$ is second order, etc.

Example 1. In a model having significant coefficient estimates on only first order terms, such as:

$$Y = a_0 + a_1 X_1 + a_2 X_2 + \dots \quad (5-4)$$

the only dependence of Y on X_1 (for example, the total slope of Y over X_1) is found by $\partial Y / \partial X_1 = a_1$. The effect of X_1 on Y is the same regardless of values of X_2 , etc., so whether X_1 is an important variable can be determined simply by testing for the significance of the coefficient estimate a_1 . This is the same test as carried out in the multiple

regression process where it is determined which terms to retain due to significance of their coefficients, and which to discard due to nonsignificance of their coefficients.

Example 2. In a model having significant coefficient estimates on any second- or higher-order terms, a separate test of significance is required. One example is a model having one two-factor interaction (whose coefficient was found to be significant) or more than one second-order term as long as the same variable doesn't appear in more than one such term, such as

$$Y = a_0 + a_1X_1 + a_2X_2 + a_{12}X_1X_2 + \dots, \quad (5-5)$$

The term X_1X_2 imparts twist to the surface. A consequence of the twist is that the total slope of Y over X_1 runs from minus infinity to plus infinity as X_2 runs from minus infinity to plus infinity. This can be seen by evaluating the total slope as

$$\partial Y / \partial X_1 = a_1 + a_{12}X_2. \quad (5-6)$$

Thus, the total slope of Y over X_1 depends on the value of X_2 . There will be a value of X_2 at which the total slope of Y over X_1 is 0. In particular, $X_2 = -a_1/a_{12}$ at $\partial Y / \partial X_1 = 0$. In Equation (5-6), a_1 and a_{12} are random variables (whose values are estimated from the data); since any function of one or more random variables is also a random variable, $\partial Y / \partial X_1$ is a random variable. A test of significance of the difference of the estimated total slope, $\partial Y / \partial X_1$, from 0 can be performed. It will be seen

below that this test will depend on the value of X_2 . Thus, there is an interval over X_2 where the estimated total slope is not significantly different from 0. At values of X_2 less than and greater than that interval, the estimates become significant. How to calculate the X_2 interval of nonsignificance of $\partial Y / \partial X_1$ at the 10% level will now be described in terms of the 90% confidence interval for true values of total slope over X_1 . That interval is

$$\left. \begin{array}{l} 90\% \text{CI, UL (+)} \\ 90\% \text{CI, LL (-)} \end{array} \right\} \text{for true total slope over } X_1$$

$$= (\text{estimated total slope, } \partial Y / \partial X_1) \pm t_{1-\alpha/2; df} s_{\partial Y / \partial X_1} \quad (5-7)$$

where 90%CI,UL = upper limit of two-sided 90% confidence interval

90%CI,LL = lower limit of two-sided 90% confidence interval

t = a value from the statistical t distribution

α = 0.10 for 90% confidence interval (also 10% significance level)

df = degrees of freedom, taken as the same as for a_1 , a_2 and a_{12} in Equation (5-5).

$s_{\partial Y / \partial X_1}$ = standard deviation of $\partial Y / \partial X_1$.

The form of Equation (5-7) is appropriate for random variables which are normally distributed. The random variable here is $\partial Y / \partial X_1$, defined in Equation (5-6). In Equation (5-6), both a_1 and a_{12} are normally

distributed, so their sum is also. Equation (5-7) is a function of X_2 , both in $\partial Y/\partial X_1$ by Equation (5-6) and in $s_{\partial Y/\partial X_1}$, as will be seen below.

$s_{\partial Y/\partial X_1}$ is evaluated by applying the propagation of errors method, generally used for deriving the variance of a function, to Equation (5-6) to obtain

$$s_{\partial Y/\partial X_1} = (s_{a_1}^2 + X_2^2 s_{a_{12}}^2)^{1/2}. \quad (5-8)$$

This is valid for a_1 and a_{12} estimated independently, as in this case due to use of an experimental design affording this advantage. That $s_{\partial Y/\partial X_1}$ is a function of X_2 can be seen in Equation (5-8).

Over values of X_2 where Equation (5-7) includes 0, the estimates $\partial Y/\partial X_1$ are not significantly different from 0 and X_1 is designated "not important" for predicting LATMS; elsewhere, $\partial Y/\partial X_1$ values are significant and X_1 is designated "important". The situation is illustrated in Figure 5-16 where the "Best Estimate" of $\partial Y/\partial X_1$ per Equation (5-6) is shown by the straight line, a function of X_2 . Typical 90%CI,LL and 90%CI,UL curves are also shown, per Equation (5-7). These define an interval over X_2 where they enclose a true value of $\partial Y/\partial X_1$ of 0. This interval is also the one where estimated values $\partial Y/\partial X_1$ are not significantly different from 0 at the 10% level. Accordingly, for X_2 values in this interval, X_1 is not important in predicting LATMS, viz, IGSCC. Outside this interval on X_2 , however, the $\partial Y/\partial X_1$ estimates are significant and X_1 is important. The X_2 intervals should be within the region where data were taken, so the model is not

being extrapolated. Also, the X_2 interval should be within the region where the plant operates, so that the X_1 importance determination is relevant to plant operation. For simplicity, assume the test and plant operating regions are the same. Figure 5-16 illustrates a case where the X_2 region where X_1 is important covers the test and plant operating region.

Example 3. Another second-order model of interest is a quadratic such as

$$Y = a_0 + a_1X_1 + a_{11}X_1^2 + \dots, \quad (5-9)$$

for which the total slope over X_1 is

$$\partial Y / \partial X_1 = a_1 + 2a_{11}X_1. \quad (5-10)$$

This model has the same considerations as the one in Example 2 except that regions of importance of X_1 are found on the X_1 scale itself, as implied by Equation (5-10), rather than on the X_2 scale. Figure 5-16 applies by changing the X_2 scale to X_1 .

Example 4. The third and last second order model to be considered is one where the same variable appears in more than one second-order term, such as X_1 appearing in two two-factor interactions in

$$Y = a_0 + a_1X_1 + a_2X_2 + a_3X_3 + a_{12}X_1X_2 + a_{13}X_1X_3 + a_{23}X_2X_3 + \dots \quad (5-11)$$

Now, the total slope of Y over X_1 is

$$\partial Y / \partial X_1 = a_1 + a_{12}X_2 + a_{13}X_3. \quad (5-12)$$

In this case, the region of importance of X_1 will be defined by pairs (X_2, X_3) as an area over both X_2 and X_3 simultaneously.

This concludes the example descriptions. The evaluation of the importance of variables in the Adopted Oxygen Model itself will now be covered.

The Adopted Oxygen Model, Equation (5-1), contains the variables TEMPC, SO4C and CO2C. Table 5-16 presents the information used in the derivation of the region of importance of each of these variables.

In Equation (5-1), TEMPC is involved in two-factor interaction terms with both SO4 and CO2C; accordingly, the importance region will involve simultaneous pairs of those two variables. This region is illustrated in Figure 5-17 relative to the test and plant operating region. It can be seen that TEMPC is important over the entire operating regions of both SO4C and CO2C; these regions were taken as -1.6 to +1.6 on the coded scale, for each variable. This can be confirmed in Figure 5-15 where there is substantial separation on the LATMS scale of the response surfaces at TEMPC = +1 and -1, even where they are least separated, at SO4C = -1 and CO2C = -1.

SO4C is involved in a two-factor interaction with TEMPC and also is in its own quadratic term, so its importance region will involve pairs of TEMPC and SO4C values. This region within -1.6 and +1.6 on TEMPC and SO4C scales

is illustrated in Figure 5-18 where SO₄C is shown to be important in the upper left part of the figure. In this region total slope is negative, which is reasonable on physical grounds. Thus, in this region, decreasing SO₄C increases LATMS, but only if TEMPC is at nominal or higher value and if SO₄C itself is at nominal or lower value. As stated previously, it can be confirmed in Figure 5-15 that the region where there is a marked negative slope of LATMS over SO₄C is at low values of SO₄C and on the TEMPC = +1 surfaces. At combinations of TEMPC more negative and SO₄C more positive, SO₄C becomes non important. Moving further in the same directions on TEMPC and SO₄C, toward the bottom right corner of Figure 5-18, the model indicates that SO₄C becomes important again but with a positive slope of LATMS over SO₄C. This is almost certainly an artifact of the quadratic model over SO₄C because the model form offered only provides for parabolic curvature. This pattern can be confirmed in Figure 5-15. In summary, in the oxygen environment, reducing sulphate can decrease IGSCC, but only if sulphate itself is at level 0 (nominal, 50 ppb) or a lower level and if temperature is at level 0 (80°C) or a higher level.

CO₂C is in a two-factor interaction with only TEMPC, so its region of importance involves only TEMPC values. Figure 5-19 shows that over most of the -1.6 to +1.6 operating region of TEMPC, namely from -1.25 to +1.25, CO₂C is not important. This can be visualized in Figure 5-15 by noting that as TEMPC moves from -1 to +1 the interaction effect of CO₂C reverses; thus, toward TEMPC = 0, the CO₂C effect is even less than illustrated. Accordingly, changing carbon dioxide is not useful in changing IGSCC.

To summarize the importance of individual variables in the oxygen environment, IGSCC can be reduced by decreasing temperature, and/or by reducing sulphate if temperature is at 80°C or greater and sulphate itself is at 50 ppb or less.

5.3.3 Analysis of the Hydrogen Peroxide Design Results and the Low Chloride-Sulphate Results

5.3.3.1 Hydrogen Peroxide Model Derivation

The hydrogen peroxide linear design results given in Table 5-10 were analyzed first to identify variables for subsequent testing in the quadratic design. With LATMS as the dependent variable, multiple linear regression analysis was performed on the 16 tests using the coded values for the dependent variables. All linear terms listed in Table 4-3 were offered for fitting; this was again done in two groups to assure that the number of test data points exceeded the number of coefficients to be estimated by at least two degrees of freedom. Terms were dropped until the coefficients on all terms remaining were significant at the 10% level as indicated by their F value's exceeding the critical F at the 90% point for the current degrees of freedom. The results of the regression analysis are given in Table 5-14 (column 5-14C). The R-squared value is 0.950, and the standard deviation of residuals is 0.136 on the LATMS scale, both comparable to the oxygen linear values and indicating a good quality of fit. The significant terms and their coefficients are also given in column 5-14C, Table 5-14. Again, by its large F value, temperature was the

dominating term and had almost the same coefficient as in the oxygen analysis. Now in the hydrogen peroxide environment, the chloride term was significant with a high F value, and the sulphate term was not significant. However, there was a temperature by sulphate interaction and also a chloride by sulphate interaction. These interactions indicate a different sulphate effect depending on the temperature level and also on the chloride level, but absence of the sulphate term itself indicates that the average sulphate effect over these variables was not significantly different from zero. Again, a coefficient was conspicuous by its absence: there was no significant effect due to hydrogen peroxide over its range tested (845 to 3,703 ppb, -1 and +1 on the coded scale).

Because oxygen was not found to be significant in analysis of the oxygen design results, the two stage method for analyzing the hydrogen peroxide data described in section 4.2 was not required. The data were analyzed by directly fitting the terms listed in Table 4-3, plus OXC (oxygen by dissociation). The two stage method had been used during preliminary analysis of the linear hydrogen peroxide data, and showed very little difference in predicted values from those obtained by fitting the data directly. Accordingly, the two-stage method was not used to obtain the adopted hydrogen peroxide model.

From the analysis of the hydrogen peroxide linear design, three variables, chloride, sulphate and hydrogen peroxide were selected for the hydrogen peroxide quadratic testing using the following rationale. The temperature effect was large, but high priority was not given to defining curvature of

the LATMS surface over temperature. This decision was influenced by the oxygen design analysis which showed no such curvature for temperature. Chloride was selected because of its high significance. Sulphate, although not significant in the hydrogen peroxide linear design, was selected on the strength of its significance in the oxygen model and due to its interaction with both temperature and chloride in the hydrogen peroxide linear design. The third variable chosen was hydrogen peroxide, again as a check on whether it would provide a significant effect when changed over a wider range of values (400 to 5,000 ppb) in the quadratic testing part. Because their coefficients were not significant, carbon dioxide and oxygen were not selected for evaluation in the quadratic testing.

The quadratic testing was carried out at the seven test conditions designated P17, P18, P21-P24 and P27 in Table 4-6. Initially, 14 specimens were tested, two replicates at each test condition using the dual-autoclave configuration of each loop. Test condition P23 was repeated using duplicate specimens because neither of the initial two specimens failed in the gauge section. In addition, center point P27 was repeated by testing one additional specimen, increasing the accuracy of the LATMS response at the center point so as to improve estimating any quadratic effects. The hydrogen peroxide quadratic design results are given in Table 5-11.

The quadratic testing added 17 data points to make a total of 33 for the combined linear and quadratic analysis. All terms in Table 4-3, except as noted, were offered for fitting the 33 data points and the results for the regression analysis of the combined hydrogen peroxide linear and quadratic

designs are given in Table 5-14 (column 5-14D). In this analysis R-squared was 0.863 and the standard deviation of residuals was 0.169, both values reflecting a slightly lower quality of fit than for the combined oxygen data (column 5-14B). This is due to greater variability between specimen pairs and to lack of model fit, especially to points P5 and P6. The same terms as in the hydrogen peroxide linear model were found to be significant, and, in addition, curvature over chloride was reflected by the significance of the chloride quadratic term. The coefficients for the temperature, temperature by sulphate interaction and chloride by sulphate interaction terms were identical to those from the hydrogen peroxide linear analysis.

A graphical representation of the data, and of the prediction model based on terms and coefficients in Table 5-14 (column 5-14D), is shown in Figure 5-20. The data points from both the linear and quadratic testing are shown, coded according to the symbols on sheet 2 of the figure. Predicted values are shown for TEMPC=-1 (55°C), the upper surface; TEMPC=0 (80°C), the center surface; and for TEMPC=+1 (105°C), the lower surface. The small solid circles represent LATMS values predicted by the model at test conditions. It can be seen in Figure 5-20, at the +1 temperature level, that the observed values for the P5 and P6 data indicate much greater increase in LATMS at the -1 levels of chloride and sulphate than predicted by the model. It was judged desirable to confirm by additional testing the marked decrease in IGSCC indicated by P5 and P6, particularly whether lower levels of chloride and/or sulphate might lead to an even greater decrease in IGSCC. Four additional tests, designated the low chloride-sulphate test

extension, were carried out at lower levels of chloride and sulphate, in the hydrogen peroxide environment at the +1 temperature level, as defined in Table 4-8.

The results of the low chloride-sulphate test extension are given in Table 5-12. A new model fitted to the 33 points in the hydrogen peroxide combined linear and quadratic designs and the four points in the low chloride-sulphate test extension gave the results which appear in Table 5-14 (column 5-14E). The inclusion of the low chloride-sulphate data resulted in a lower R-squared value, 0.829, and a greater standard deviation of residuals, 0.183, when compared to the values for the combined linear and quadratic data alone (column 5-14E compared to column 5-14D in Table 5-14). This lower quality of fit is due to finding that points P5 and P6 are somewhat higher than the surface fitted to the two data sets, and generally to lack of model fit, that is, to the relatively simple model form available for fitting. Nevertheless, a number of terms have significant coefficients, based on their F value's exceeding the critical F, and the model itself is highly significant. Importance of the variables themselves is discussed in section 5.3.3.3.

Using the coefficient data from Table 5-14 (column 5-14E), the prediction equation using terms on the coded scale for the hydrogen peroxide environment is given below.

Adopted Hydrogen Peroxide Model

$$\text{LATMS} = 1.811$$

$$-0.237 \times \text{CLC}$$

$$-0.418 \times \text{TEMPC}$$

$$-0.107 \times \text{TEMPC} \times \text{SO4C}$$

$$+0.0661 \times \text{CLC} \times \text{SO4C}$$

$$+0.0787 \times (\text{CLC})^2 \quad (5-13)$$

This prediction equation, using variables on the physical scale, is given below.

$$\text{LATMS} = 4.993$$

$$-0.1553 \times \text{CLE}$$

$$-0.03646 \times \text{TEMP}$$

$$-1.799 \times \text{SO4E}$$

$$+0.04071 \times \text{TEMP} \times \text{SO4E}$$

$$-0.3285 \times \text{CLE} \times \text{SO4E}$$

$$+0.02149 \times (\text{CLE})^2 \quad (5-14)$$

For both Equations (5-13) and (5-14) the symbol for each variable is as follows:

	(5-13)	(5-14)	(5-14)
	Coded	Physical	Physical
	Scale	Scale	Values with
			Exponents
Log ₁₀ (Adjusted Time to Maximum Stress)	LATMS	LATMS, Log hours	----
Chloride Concentration	CLC	CL, ppb	CLE
Temperature	TEMPC	TEMP, °C	----
Sulphate Concentration	SO4C	SO4, ppb	SO4E

where $CLE = CL^{0.43815}$ and $SO4E = SO4^{-0.18508}$

5.3.3.2 Graphical Representation of the Adopted Hydrogen Peroxide Model

A graphical representation of the data, and of the prediction model with terms on the coded scale, is shown in Figure 5-21 which for clarity is separated into Figures 5-21A and 5-21B. Figure 5-21A shows the -1 and 0 temperature levels (55°C and 80°C respectively) while Figure 5-21B shows the 0 and +1 temperature levels (80°C and 105°C respectively). In Figure 5-21A the data from the hydrogen peroxide linear testing at the -1 temperature level, are shown at test conditions P1-P2, P3-P4, P9-P10 and P11-P12. From the quadratic testing performed at 0 temperature level, data for the star points at +1.6 and -1.6 levels on the chloride scale are shown

at P17 and P18, and at +1.6 and -1.6 levels on the sulphate scale at P21 and P22, all other variables at 0 level.

The prediction surface related to the hydrogen peroxide linear design testing at TEMPC = -1 is shown by the four broken lines. Predicted values for the particular test conditions are identified by the small solid circles near the data points. Similarly for the hydrogen peroxide quadratic design testing, the related prediction surface is indicated by the two dashed lines; it, too, has small solid circles for test condition predictions. The TEMPC = 0 surface lies below the one at TEMPC = -1, as indicated by the predicted values at TEMPC = 0 and -1 on the center stem.

The effect of the terms in the adopted hydrogen peroxide model can be seen as follows. The large separation of the two predicted values on the center stem reflects the highly significant temperature effect. The effect of chloride, the term having the second most significant coefficient, is seen by the very steep slope (exceeding 45°) of the dashed line over the chloride scale at TEMPC = 0; it is curved due to the chloride-squared term in the model. The slope does not change between TEMPC = 0 and TEMPC = -1 at the zero level of sulphate, but it increases as sulphate decreases (visible at TEMPC = -1), a consequence of the chloride by sulphate interaction term. The dashed prediction line for sulphate at TEMPC = 0 is parallel to the sulphate axis, indicating no average effect of sulphate. However, at TEMPC = -1 the prediction slope is positive. This rotation was unexpected, but it is clearly set by the relationship between points P9-P10 and P11-P12 at the +1 chloride level, TEMPC = -1. The nearly horizontal

relationship between points P1-P2 and P3-P4 at the -1 chloride level, TEMPC = -1, calls for twist in the prediction surface over the chloride and sulphate scales, again reflecting the chloride by sulphate interaction term in the model.

Figure 21B covers the 0 and +1 temperature levels (80°C and 105°C) in the hydrogen peroxide designs and the low chloride-sulphate test extension. At the zero level of temperature, the quadratic design data points from Figure 5-21A, P17-P18 and P21-P22, are repeated. In addition, the data points for test conditions P23, P24 and P27 are shown on the center stem. Data points P23 and P24 are for the +1.6 and -1.6 levels of hydrogen peroxide, all other variables at their zero level, and P27 is the center point test condition. At the +1 temperature level, the data from the hydrogen peroxide linear design are shown at test conditions P5-P6, P7-P8, P13-P14 and P15-P16. The data from the low chloride-sulphate test extension are at P48, P50, P51 and P52.

The prediction surface related to the TEMPC = 0 quadratic test conditions is identified by the dashed lines, as in Figure 5-21A. These lines lie above the solid prediction lines at TEMPC = +1 (as can be confirmed by noting where the two surfaces cross the center stem). The dashed line over the chloride scale is curved to pass near the mean of data at P23, P24 and P27 relative to P17 and P18. Small solid circles are predicted values for the adjacent test conditions. The LATMS prediction surface for TEMPC=+1 is shown by solid lines and spans not only -1 to +1 levels on both chloride and sulphate scales, but is extended to the -1.6 level on the chloride

scale and to the -2.0 level on the sulphate scale in order to show the predicted values for P48, P50-P52. Predicted values for the test conditions are again shown by small solid circles at the four combinations of -1 and +1 on the chloride and sulphate scales, and at the extensions for P48, P50-P52.

Effects of the terms in the prediction equation can be seen in Figure 5-21B as follows. The strong temperature effect is shown by the separation of the small solid circles on the center stem at TEMPC values marked "0" and "+1". The chloride effect is shown by the dashed and solid lines over the chloride scale at 0 sulphate level exceeding 45° in slope. Slope over the chloride scale increases as sulphate changes from +1 to -2 level, introducing twist reflecting the chloride by sulphate interaction. The lines over the chloride scale are curved due to the chloride squared term. Finally, the absence of an average sulphate effect is shown by the dashed line horizontal over the sulphate scale at TEMPC=0, as in Figure 5-21A, but the temperature by sulphate interaction is shown again by the change from zero slope over sulphate at TEMPC=0 to a negative slope over sulphate directly beneath that dashed line on the line marked "CLC=0" in the TEMPC=+1 surface. Thus, at the +1 temperature level, there is a reduction in IGSCC toward reduced sulphate levels.

It can be seen that for the model to accomodate all of the data in a least-squares manner it had to pass below P5 and P6 as it did in figure 5-20. However, at TEMPC = +1, there is a clear increase in LATMS toward both the -1.6 chloride level and the -2.0 sulphate level, reflecting

decreasing IGSCC toward those levels (2 ppb chloride and 7 ppb sulphate). The data show that these are the most advantageous levels tested, and the model indicates that even less IGSCC may accompany further reductions in chloride and sulphate, at the +1 temperature level (105°C). The reduction of IGSCC by reducing sulphate is not predicted for TEMPC = 0 or -1, 80°C or 55°C.

At all temperature levels, the coded data points in Figures 5-21A and 5-21B for the -1 and +1 levels of hydrogen peroxide were not sufficiently separated for the hydrogen peroxide term to be significant. For the same reason the carbon dioxide term was not significant.

The large effect of temperature alone on LATMS in both oxygen and hydrogen peroxide environments is illustrated by the steepness of the lines in Figure 5-22. The lines represent the adopted models themselves, so they fit the points. Each plotted point is the average LATMS value from the number of test conditions shown beside the point. The test conditions selected for averaging in each plotted point are balanced in the variables, other than temperature, which are involved in terms having significant coefficients; they may not be balanced in the remaining variables. This means that in the oxygen model, for example, for evaluating each average LATMS point plotted, there are the same number of test conditions having SO4C at -1 as at +1, or CO2C at -1 as at +1, or SO4C at -1.6 or +1.6, because SO4C and CO2C are the variables, besides TEMPC, which are involved in terms having significant coefficients in that model. There may not be balance in CLC or OXC. This balance is important because, without it, the

mean would be shifted away from its true location just by the effect of some variable other than temperature itself. The same rule was used to select test conditions for each point plotted for the hydrogen peroxide model; for it, the variables present in a balanced manner are CLC and SO₄C. There may not have been balance in PEROX or CO₂C. The prediction lines in Figure 5-22 are from the models themselves, all other variables besides TEMPC at their 0 levels. It can be seen in Equations (5-1) and (5-13) that the coefficients on TEMPC are nearly identical; thus, the two lines are nearly parallel. They are also quite steep, reflecting the high significance of the coefficients on TEMPC in each model.

A comparison between the adopted oxygen and hydrogen peroxide models is made in Figure 5-23. Predicted LATMS surfaces are shown at the -1 and +1 temperature levels (55°C and 105°C); the oxygen predictions are shown by the broken lines and the hydrogen peroxide predictions by the solid lines. At the +1 chloride level (68 ppb) there is a substantial effect of the presence of hydrogen peroxide (exceeding 400 ppb hydrogen peroxide compared to the absence of hydrogen peroxide in the oxygen environment) at both temperature levels and at both sulphate levels (17 ppb and 187 ppb): the presence of hydrogen peroxide reduces LATMS and thus increases IGSCC. However, at the -1 chloride level (8 ppb), predicted LATMS values on the hydrogen peroxide surface coincide with those on the oxygen surface at both temperature levels. Thus, there is an average effect of the presence of hydrogen peroxide which is significant, as indicated by the separation of the solid circles marked "Ox" and "Per" on the center stem, at both temperature levels; but in reality, the presence-of-hydrogen peroxide

effect is substantial at the +1 chloride level (68 ppb) but vanishes as chloride decreases to the -1 level (8 ppb). The agreement of oxygen and hydrogen peroxide predictions at the -1 chloride level is one kind of confirmation that the observed values of P5 and P6 are high relative to the other data. Figure 5-23 is drawn for $OXC = PEROXC = CO2C = 0$.

5.3.3.3 Importance of Individual Variables in the Adopted Hydrogen Peroxide Model

The adopted hydrogen peroxide model can identify which physical variables in the hydrogen peroxide environment are important in determining IGSCC of sensitized Type 304 stainless steel. The method used is to associate the region where variable X_i is important with the region where the total slope of LATMS over X_i , $LATMS/X_i$, is significantly different from zero at the 10% level, following the principles described in section 5.3.2.3. The results are as follows.

The adopted hydrogen peroxide model, Equation (5-13), contains the variables CLC, TEMPC and SO4C. Table 5-17 presents the information used in derivation of the region of importance of each of these variables, as required in Equation (5-7).

In Equation (5-13), CLC appears in three terms, one by itself, one in a two-factor interaction with SO4C, and one in its own quadratic; thus, the region of importance of CLC will involve simultaneous pairs of values of SO4C and CLC. The region of importance of CLC, over the operating range of

-1.6 to +1.6 for SO4C and CLC, is shown in Figure 5-24. CLC is important when CLC itself is at or less than coded level 0, over all values of SO4C from -1.6 to +1.6. For values of SO4C at level 0 or less, CLC is important when its own level is at or less than 0.7 (or slightly more). Total slope of LATMS over CLC is negative, so decreasing CLC in its region of importance increases LATMS, i.e. decreases IGSCC as expected. This pattern can be seen in Figures 5-21A and 5-21B where the slope of LATMS over CLC is seen to be sufficiently great to be significant, for CLC less than level 0 over all SO4C values from levels -1.6 to +1.6.

In Equation (5-13), TEMPC appears in two terms, one by itself and one in a two-factor interaction with SO4C, so the region of importance of TEMPC will involve values of SO4C. It was found that TEMPC is important over all values of SO4C in the operating range from -1.6 to +1.6. Total slope of LATMS over TEMPC is negative, so decreases in TEMPC increase LATMS. This can be confirmed in Figures 5-21A and 5-21B where the increases in LATMS from TEMPC = +1 (in Figure 5-21B) to TEMPC = -1 (in Figure 5-21A) are sufficient over all values on the SO4C scale from -1.6 to +1.6 that the corresponding total slopes are significant.

In Equation (5-13), SO4C appears in cross-product terms with CLC and TEMPC (though not in any terms of its own). Thus, the region of importance will involve values of CLC and TEMPC. This region is shown in Figure 5-25 and involves CLC values mainly less than level 0 and TEMPC values greater than level 0.6 (95°C). In this region, total slope of LATMS over SO4C is negative, so lower values of SO4C increase LATMS and thus decrease IGSCC.

This region can be confirmed in Figures 5-21A and 5-21B by noting that the slope of LATMS over SO₄C is markedly negative only where TEMPC = +1 and CLC is negative. Figures 5-21A and 5-21B show that (at CLC= 0) there is no slope of LATMS over SO₄C, and Figure 5-21A shows that this slope has become positive at TEMPC = -1. Thus, IGSCC susceptibility can be reduced by decreasing sulphate, but only if chloride is at or less than nominal (30 ppb) and temperature exceeds 95°C.

Whether the presence of hydrogen peroxide is important was also determined. This was done by creating a new random variable, LATMS, as the difference between the adopted hydrogen peroxide and oxygen models, as

LATMS - Presence-of-hydrogen peroxide effect

$$\begin{aligned}
 &= \text{LATMS (H}_2\text{O}_2 \text{ Environment)} - \text{LATMS (O}_2 \text{ Environment)} \\
 &= \text{Adopted H}_2\text{O}_2 \text{ Model (TEMPC, SO}_4\text{C, CO}_2\text{C)} - \text{Adopted O}_2 \\
 &\quad \text{Model (CLC, TEMPC, SO}_4\text{C)}
 \end{aligned}
 \tag{5-15}$$

The presence of hydrogen peroxide is an important variable as long as not only the best estimate, LATMS, is negative, but the upper limit of the 90% confidence interval on the true LATMS is negative. This value is found as

Upper limit of 90% Confidence Interval on true LATMS

$$= \text{LATMS} + t_{0.95, df}^s \text{ LATMS}$$

where: LATMS is found by Equation (5-15)

df = average degrees of freedom of the two models = 27

$t_{0.95,df} = 1.7$

s LATMS is found by propagation of errors on Equation (5-15). All coefficient estimates in both models are independent.

The behavior of LATMS over CLC and SO4C, and also TEMPC, can be visualized in Figure 5-23 as the difference between the two surfaces shown. Equation (5-15) shows that, between the two models, LATMS depends on CLC, TEMPC, SO4C and CO2C. The importance analysis revealed, however, that LATMS is important for CLC from levels -0.8 to +1.6 over the entire test and operating range of -1.6 to +1.6 of the other three variables. It can be seen in Figure 5-23 that separation of the surfaces of the two models may be sufficient for this importance only for CLC exceeding -0.8, not changing for the other three variables.

To summarize, IGSCC in the hydrogen peroxide environment can be reduced by decreasing chloride if sulphate is also less than nominal (50 ppb) (regardless of temperature); by decreasing temperature; and by decreasing sulphate if chloride is less than nominal (30 ppb) and temperature exceeds 95°C. IGSCC can also be reduced by eliminating hydrogen peroxide from the environment entirely, for chloride concentration exceeding 11 ppb.

5.3.4 Additional Studies

5.3.4.1 Results of Option 1 Tests and their Correlation with the Hydrogen Peroxide Model and Oxygen Model

The results from the Option 1 tests performed in the hydrogen peroxide environment are given in Table 5-13 as test condition numbers 1-11. The correlation of these data with their predicted values using the hydrogen peroxide model is shown in Figure 5-26. The predicted values are shown by small solid circles. Tests were performed at one of four temperature levels, -1.8 (35°C), -0.08 (78°C), +0.8 (100°C) or +1.6 (120°C), as indicated by symbols in Figure 5-19; at one of three combinations of levels of chloride and sulphate, both at -1.6, or 0, or +1.6; and at levels between -1.6 and +1.6 on the hydrogen peroxide, carbon dioxide and oxygen scales. As indicated in Table 5-13, in test conditions 1 to 10 the oxygen level was obtained by a combination of oxygen gas addition and hydrogen peroxide dissociation. In test condition 11 just the oxygen from hydrogen peroxide dissociation was present. It can be seen from Figure 5-26 that the predicted values are in reasonable agreement with the data. However, they have greater variability than the data on which the hydrogen peroxide model was based. There are two possible reasons for this. First, most of the Option 1 tests were performed at extreme levels of several variables simultaneously where predicted values may be less accurate than they would be toward center conditions. Second, the Option 1 test results were not used in defining the model and therefore did not influence the original fit.

As an additional check, a model with the Table 4-3 terms was fitted to both the 37 points in the hydrogen peroxide model data base and the 11 points in the Option 1 testing. The same terms were found to have significant coefficients; slopes over both temperature and chloride were slightly less, leading to less extreme predicted values at increasing departures from center conditions. The greatest difference in any one predicted value in Figure 5-21 (A and B) was 0.160 log hours for both P3-P4 and P15-P16.

There was one Option 1 test in the oxygen environment, test condition 12 in Table 5-13. It can be seen that its LATMS value of 2.05 falls very close to the predicted value at TEMPC = 0 on the center stem in Figure 5-15. Thus, this Option 1 point is consistent with results of the oxygen linear and quadratic testing.

5.3.4.2 Validation of the Hydrogen Peroxide Model

The Option 1 data can be used to carry out the statistical process of "validation" of the hydrogen peroxide model. One method is to see whether the mean and standard deviation of the differences between observed and predicted values in an independent data set (i.e. Option 1 tests) differ significantly from those values in the data set on which the model was based. The means and standard deviations of data relative to predicted values on the LATMS scale are as follows:

	<u>Mean</u>	<u>Standard Deviation</u>	Number of of data
Original fit of			
hydrogen peroxide model	Residual: 0	0.183	37
Predictions of			
Option 1 data by			
H ₂ O ₂ model	Difference: 0.0194	0.283	11

The difference between the two means is far from significant at the 10% level; the two standard deviations are significantly different at the 10% level but not at the 5% level. Accordingly, the hydrogen peroxide model can be considered validated by the Option 1 data.

5.3.4.3 Loop Effect in the Hydrogen Peroxide Environment

To address whether any of the four test loops produced consistently high or low LATMS values, the 37 hydrogen peroxide environment values were fitted with a model in which the terms in Figure 5-14 (column 5-14E) were forced to be present, and the following terms were also offered:

(Absence of Indicator Variable for Loop A)

Indicator Variable for Loop B

Indicator Variable for Loop C

Indicator Variable for Loop D

Observed Oxygen by Dissociation

The ECP of the Stainless Steel Electrode (ECP-SS)

Indicator variables provide for a different intercept (elevation of the surface) when a particular condition is present compared to when it is not present; coefficients on the regular variables are estimated in common. From the foregoing terms, only Loop D was significant. This effect for the five Loop D points (tested in the hydrogen peroxide environment) is an accommodation of points P5 and P6, and P9 relative to P10 (Figure 5-21A). Data points P1 and P2 (Figure 5-21A) do not appear out of place, but they too would now take the Loop D prediction. The sixth Loop D point, O3 in the oxygen testing, also does not appear inconsistent with the remainder of the oxygen data (Figure 5-15). A Loop D intercept-change term was not included in the model for the following reasons:

1. There was no clear physical reason for some test times to be longer in Loop D. Owing to a larger de-oxygenation system, this loop exhibited lower levels of dissociated oxygen than Loops A, B or C, as shown in Figure 5-27; these ranged between 47 and 130 ppb oxygen (Table 5-10). However, changes in oxygen level over a wide range (100 to 8000 ppb) had been shown to have no significant effect on LATMS in the oxygen environment.

2. Including a Loop D intercept change in the hydrogen peroxide model would markedly decrease the predicted value at the -1 level for chloride, temperature and sulphate, so it would introduce an inconsistency with the oxygen-model predictions at the -1 chloride level in Figure 5-23.
3. Including the same Loop D intercept change term in the oxygen model would introduce one or more inconsistencies in the predicted values of that model.
4. The conclusions of Task A would not be affected.

There were no significant LATMS differences among Loops A, B and C. The effects of observed oxygen from hydrogen peroxide dissociation and of ECP-SS, additional to the adopted hydrogen peroxide model with the Loop D term, also were not significant.

5.3.4.4 Effect of ECP-SS Alone

The LATMS values were fitted to the 30 oxygen data and separately to the 37 hydrogen peroxide data using the ECP of Type 304 stainless steel as a single variable (ECP-SS). The relationship between LATMS and ECP-SS is shown graphically in Figure 5-28 for the oxygen design tests and in Figure 5-29 for the hydrogen peroxide design tests. Although it is clear that the average ECP-SS in the hydrogen peroxide environment is greater than in the oxygen environment, the ECP-SS was found to be not significant in either

environment. Thus, ECP-SS cannot be used to predict LATMS in the oxygen environment, or in the hydrogen peroxide environment.

5.3.4.5 Repeatability of Oxygen and Hydrogen Peroxide

Environment Data

Duplicate testing of specimens in the quadratic parts of the oxygen and hydrogen peroxide designs provided an opportunity to evaluate the variability of data in these two environments. The two measures of repeatability, as standard deviations, are as follows:

<u>Environment</u>	Number of Pairs of Data	Repeatability, as Standard Deviation on the LATMS scale
Oxygen	6	0.07038
Hydrogen Peroxide	7	0.1583

There was greater variability in the hydrogen peroxide environment; the two standard deviations are significantly different at the 10% level by the two-sided F test. This indicates that testing in the hydrogen peroxide environment was characteristically more variable than in the oxygen environment.

5.3.5 Summary of Data Analysis and Interpretation

The data analysis objective was to define a model (a mathematical equation) for predicting IGSCC in terms of selected SRP reactor environmental variables. These variables, defined by SRP, included temperature and concentrations of chloride, sulphate, hydrogen peroxide, oxygen and carbon dioxide. To carry out the analysis a CERT parameter was defined to serve as a measure of IGSCC of the Type 304 stainless steel specimens.

Time-to-failure and the ductility measurements of percent elongation and percent reduction of area are typical recorded parameters from CERT tests. Each of these could have been used independently as a CERT parameter. However, several specimens failed in shoulder regions and others failed in tab-ends. In the latter case, CERT load-time graphs exhibited a marked drop in load, corresponding to tab-end cracking, followed by a load increase before final failure of the specimen. Thus, in these specimens, time-to-failure was not considered representative of IGSCC. In other works, interrupted CERT tests have shown that IGSCC initiates at a time close to that when the maximum load occurs. Therefore, for these two reasons, time to maximum stress (load/cross sectional area) was chosen as the basis for the CERT parameter. Time to maximum stress for each CERT test was plotted versus ductility (% elongation + % reduction of area) (Figure 5-12) and versus maximum stress itself (Figure 5-13). From each of these two plots, an adjusted time to maximum stress was obtained for each specimen and these two values were averaged to obtain an average time to maximum stress for each specimen. The logarithm of the latter value for

each specimen was taken and this defined the CERT parameter LATMS (Log Adjusted Time to Maximum Stress). Statistical analysis of test results was based on this CERT parameter, LATMS.

A desirable model form is linear in coefficients on first-degree terms (eg. X_i , independent variables), on two-factor interactions (eg. $X_i X_j$) and on second-degree (quadratic) terms (eg. X_i^2). This model form permits the test data to be analyzed by linear multiple regression and coefficients to be estimated by the least-squares criterion. Therefore, an experiment design of the "central composite" type was defined (section 4.2). This design allowed independent estimates of the coefficients and produced coefficient estimates having minimum error. The design was in two parts: a linear part and a quadratic part, and was adaptive in nature. The adaptability allowed the number of CERT tests to be kept to a minimum; only terms found significant in the linear part were run in the quadratic part. Hydrogen peroxide dissociates, resulting in oxygen formation. therefore it was impossible to maintain independence between the independent variables hydrogen peroxide and oxygen in a single experiment design. Therefore two designs were used, one designated "oxygen design" and the other "hydrogen peroxide design". Both of these designs had linear and quadratic parts. The oxygen design did not incorporate hydrogen peroxide, and conversely, the hydrogen peroxide design did not incorporate additional oxygen above that produced by dissociation. Five independent variables were included in the linear part tests and analysis of these results allowed the number of independent variables to be reduced to three in the quadratic part tests.

The CERT testing was run in the following parts: oxygen design linear part, hydrogen peroxide design linear part; each of these consisted of one-half fractional factorials of five independent variables at two levels requiring 16 tests per design; oxygen design quadratic part, hydrogen peroxide design quadratic part; each of these incorporated three independent variables with each test condition duplicated requiring 14 tests per design; and, an additional four tests to evaluate low chloride and low sulphate concentrations. Statistical analysis of the test data (LATMS values) from each part followed the same procedure. In fitting LATMS values by multiple linear regression, all terms were initially offered and those whose coefficient estimates were "not significant at the 10% level" were dropped. The F-distribution value for 10% level of significance and the degrees of freedom involved was used for the test of significance. The "dropped" terms were considered not important in predicting IGSCC. Table 5-14 summarizes the results of the regression analyses. The quality of fit was reflected in the R-squared value, the square of the multiple correlation coefficient sometimes called the "index of determination"; the closer this value is to 1 the better the model fits the data. Values of 0.95 obtained for both linear oxygen and hydrogen peroxide designs reflect a good quality of fit.

The fitting of LATMS values by the foregoing procedure was carried out five times: on the oxygen linear design data to select variables for the oxygen quadratic design; on the oxygen linear and quadratic design data combined to produce the adopted oxygen model; on the hydrogen peroxide linear design data to select variables for the quadratic design; on the hydrogen peroxide

linear and quadratic design data combined and on those data together with data from the low chloride-low sulphate tests to produce the adopted hydrogen peroxide model.

The prediction equations for these models relating LATMS to environmental variables (and their interactions) having significant coefficient estimates are given in Equations (5-2) (oxygen model coded scale), (5-3) (oxygen model physical scale), (5-13) (hydrogen peroxide model coded scale) and (5-14) (hydrogen peroxide model physical scale). From these equations, LATMS values (IGSCC) can be predicted as a function of temperature and environmental variables within the temperature range and concentration ranges evaluated in the tests. In those equations, coefficients which have negative signs indicate that a decrease in that independent variable, two-factor interaction or quadratic term will produce an increase in LATMS, i.e. a decreased IGSCC. Conversely, for a decrease in an independent variable, coefficients with positive signs contribute to decreasing LATMS and increasing IGSCC. With reference to the adopted hydrogen peroxide model (Equation (5-13)), the first two terms have negative coefficients. These indicate that decreasing chloride concentration or temperature increases LATMS and thereby decreases IGSCC. The temperature-sulphate interaction term also has a negative coefficient. This term indicates that a decrease in temperature at high sulphate concentration is more effective in increasing LATMS (decreasing IGSCC) than at low sulphate concentration; and also, a decrease in sulphate concentration at high temperature is more effective in increasing LATMS than at low temperature. The chloride-sulphate interaction term has a positive coefficient. This term

indicates that a decrease in chloride concentration at low sulphate concentration more effectively increases LATMS (decreases IGSCC) than at high sulphate concentration; and also, a decrease in sulphate concentration at a low chloride concentration more effectively increases LATMS than at high chloride concentration. Finally, the CLC squared term (quadratic) has a positive coefficient. This term indicates that decreasing chloride concentration at already low concentration more effectively increases LATMS (decreases IGSCC) than does decreasing chloride concentration at high concentrations of chloride.

The prediction equations were used to define graphical "response surfaces" for both the oxygen design and the hydrogen peroxide design. These response surfaces visually show the effect on LATMS of variables which have significant coefficient estimates. For example, the response surfaces obtained from the adopted hydrogen peroxide model (Equation (5-13)) are shown in Figures 5-21A and 5-21B. The effect of temperature on LATMS (hence IGSCC) can be seen by the separation of response surfaces at 55°C, 80°C and 105°C. The effects of an individual variable (linear terms), such as chloride, is shown by the slope of the response surface as the concentration of that variable changes. The effect of two-factor interaction terms is reflected in response surface twist and quadratic terms produce curvature in the response surface.

When the slope, twist and curvature of a response surface are taken together it can be envisioned that the response surface slope may be steep enough to be significant over only a portion of one or more of the

independent variable scales. To address this, an "importance analysis" was performed to identify the ranges over which an independent variable is important. This analysis was performed for individual variables in (1) the adopted oxygen model (section 5.3.2.3) and, (2) the adopted hydrogen peroxide model (section 5.3.3.3). In the analyses, a variable was designated "important" if the "total slope" (Equation 5-3) of LATMS over that variable was found to be significant at the 10% level. The adopted hydrogen peroxide model, Equation (5-13), will be used for illustration of the importance concept. In that equation, CLC (chloride on coded scale) appears in three terms, one by itself, in a two-factor interaction with sulphate, and in its own quadratic term. Thus, the region of importance will involve simultaneous pairs of values of SO₄C (sulphate on coded scale) and CLC; the predicted region of importance is shown in Figure 5-24. It can be seen that CLC is important when CLC itself is at or less than coded level 0, over all values of SO₄C from coded level -1.6 to coded level +1.6. For values of SO₄C at coded level 0 or less, CLC is important when its own level is at or less than about the coded level +1.2.

The quantitative importance of each variable in decreasing IGSCC has been summarized in the next section in Table 6-1. In the hydrogen peroxide environment, chloride is important over the range 2 to 30 ppb (the lower coded level -1.6 to level 0) on its own scale, over all values in the respective coded ranges of temperature, sulphate, and carbon dioxide scales. Temperature is important at all values over all scales; i.e. chloride, temperature, sulphate and carbon dioxide. Sulphate is important over the range 2 to 30 ppb on the chloride scale, over 95°C to 120°C on the

temperature scale (coded levels +0.6 to +1.6), and over all values on the sulphate and carbon dioxide scales. Carbon dioxide, hydrogen peroxide itself and dissociated oxygen were found to be not important in the hydrogen peroxide environment. A comparison of the adopted oxygen and hydrogen peroxide models shows that the presence of hydrogen peroxide above 400 ppb (above lower coded level -1.6) is important when chloride is in the range 11 to 100 ppb (coded levels -0.8 to +1.6) and significantly (at the 5% level) increases IGSCC.

Overall, the prediction models show that an improved reactor environment, one that decreases Type 304 stainless steel IGSCC, can be achieved by reducing chloride and sulphate concentrations; and, within constraints dictated by reactor operation, by decreasing operating temperature and/or eliminating hydrogen peroxide entirely if the chloride concentration is less than 11 ppb.

Table 5-1. Cart Test Results for Option 1 Study

Specimen Number	Heat Treatment (a)	Loop Environment (b)	Time to Failure (Hours)	Maximum Breaking Stress (Ksi)	E (Z)	RA (Z)	Fracture Mode (ZIGSCC)
2A20	VS	A-Low Levels	386	91.7	56.6	71.5	0
2A21	VS	A-Low Levels	386	100.2	59.9	71.0	0
2A22	VS	B-Nominal	55	41.9	6.4	8.0	92
2A94	VS	B-Nominal	52	44.4	3.7	2.3	100
2A18	FS	B-Nominal	50	44.5	3.8	7.8	100
2A19	FS	B-Nominal	50	50.3	4.1	4.0	100
2A95	VS	C-High Levels	38	34.6	2.5	4.3	100
2A96	VS	C-High Levels	30	31.3	2.4	3.3	100
2A17	FS	C-120, Others Low	115	51.0	10.7	19.7	89
2A91	FS	A-35, Others High	361	90.8	53.3	63.5	0
2A92	FS	B-78, Nominal (c)	81	48.9	7.4	12.6	98
2A93	FS	C-78, Nominal (d)	140	57.8	12.6	24.4	94

(a) VS - Simulated Weld Sensitized, 15H/600
FS - Furnace Sensitized, 24H/600

(b) ECP (mV vs SHE)

Low Levels: +400

Nominal Levels: +560

High Levels: +520

(c) Oxygen resulting from decomposition of H_2O_2

(d) Oxygen added as gas; no H_2O_2

TABLE 5-2. Task A. Linear Oxygen Design Cert Test Results

Specimen No.	Temp. (°C)	O ₂	H ₂ O ₂	Variable Levels		CO ₂	Failure Time		Maximum Breaking Stress		Time-to-Maximum Stress		RA (Z)		Fracture Mode		ECP (mV vs SHE)
				CL	SO ₄ ²⁻ (ppb)		(h)	(h)	(Ksi)	(h)	(h)	(h)	(Z)	(Z)	(XIGSCC)	(304 Pt)	
2A38	55	244	0	8	17	82	374	81.1	336	38.9	58.6	22	258	600			
2A69 (a)	55	244	0	68	17	683	495	80.5	443	44.8	68.2	0	267	599			
2A64	55	244	0	8	187	683	520	83.4	460	45.2	59.6	0	186	645			
2A26	55	244	0	68	187	82	274	96.1	214	24.1	26.6	67	233	650			
2A98	55	3755	0	8	17	683	593	81.9	519	47.8	66.8	0	391	679			
2A97	55	3755	0	8	187	82	434	82.3	374	40.3	64.8	3	381	644			
2A105	55	3755	0	68	17	82	389	76.3	238	ND	ND	ND	336	660			
2A31	55	3755	0	68	187	683	484	82.5	414	43.2	68.0	0	365	635			
2A52	105	244	0	8	17	683	121	48.6	66	12.1	10.2	98	205	595			
2A29	105	244	0	8	187	82	57	41.5	30	4.9	ND	100	260	579			
2A33	105	244	0	68	17	82	129	57.6	78	11.5	17.0	87	110	579			
2A49	105	244	0	68	187	683	75	47.6	52	5.3	9.9	100	212	605			
2A47	105	3755	0	8	17	82	104	55.0	82	9.5	15.4	100	302	605			
2A35	105	3755	0	8	187	683	46	41.1	28	2.6	6.4	100	280	655			
2A50	105	3755	0	68	17	683	72	47.2	48	5.5	12.1	100	270	625			
2A23	105	3755	0	68	187	82	52	42.4	34	4.7	8.9	100	323	635			

(a) Tested in MDM Lab

(b) ND - Not Determined; Specimen Failed in End Tab or Neck Region of Gage Section

TABLE 5-3: Task A. Linear Hydrogen Peroxide Design Cert Test Results

Specimen No.	Temp. (°C)	O ₂ (b)	Variable Levels		CO ₂	Maximum		Time-to-Failure (h)	Time-to-Maximum		RA (c) (X)	Fracture Mode (XIGSCC)	ECP (mV vs SHE)
			H ₂ O ₂	CL ⁻ SO ₄ ²⁻ (ppb)		Failure Stress (ksi)	Stress (h)		Stress (h)	(X)			304 pt
2A24 (a)	55	62	845	8	17	81.6	460	500	56.4	46.2	0	444	503
2A42 (a)	55	120	845	8	187	81.5	347	455	50.4	ND	ND	620	508
2A30 (a)	55	47	845	68	17	68.7	128	146	15.9	22.8	72	450	517
2A25 (a)	55	500	845	68	187	70.6	182	207	16.5	ND	ND	645	587
2A56 (a)	55	129	3703	8	17	82.7	417	526	47.9	60.3	0	577	497
2A65	55	1650	3703	68	17	57.1	73	107	9.8	20.3	95	672	495
2A37	55	1600	3703	8	187	81.5	454	472	47.1	67.5	0	685	511
2A58	55	1000	3703	68	187	70.2	178	301	14.7	ND	ND	525	484
2A61 (a)	105	59	845	8	17	68.4	178	202	22.7	32.8	74	473	494
2A68	105	450	845	68	17	45.9	38	58	4.4	4.5	100	512	466
2A7	105	600	845	8	187	41.4	36	56	6.0	8.4	100	580	478
2A99 (a)	105	800	845	68	187	36.1	22	36	2.6	3.3	100	588	497
2A34 (a)	105	130	3703	8	17	62.7	142	187	15.7	ND	100	489	445
2A102	105	2200	3703	68	17	35.4	20	41	4.0	2.9	100	593	563
2A57	105	1600	3703	8	187	35.5	20	26	2.0	3.1	100	525	484
2A101	105	1900	3703	68	187	34.2	16	34	3.6	2.4	100	651	659

(a) Tested in MOM Lab

(b) No O₂ Added; Value Resulting from Dissociation of H₂O₂

(c) ND - Not Determined; Specimen Failed in End Tab

TABLE 5-4. Task A. Quadratic Oxygen Design Cart Test Results

Specimen No.	Temp. (°C)	Variable Levels (ppb)			CO ₂	Failure Time (h)	Maximum Breaking Stress		RA (a) (X)	Fracture Mode		ECP (mV vs SHE) 304 Pt
		O ₂	H ₂ O ₂	CL S ₂ O ₄			(Ksi)	(h)		(X)	(XIGSCC)	
2A28	80	1000	0	30	50	300	56.3	111	7.7	ND	ND	333 593
2A66							58.8	95	ND	ND	100	
2A48	80	1000	0	30	500	300	67.6	128	14.5	ND	69	287 656
2A90							72.4	166	20.0	30.2	60	
2A60	80	1000	0	30	10	300	76.1	181	ND	ND	ND	315 625
2A62							75.4	241	27.8	53.6	30	
2A10	80	8000	0	30	50	300	73.8	211	21.6	33.9	88	420 690
2A39							67.5	148	15.6	28.2	98	
2A44	80	100	0	30	50	300	62.3	107	11.3	28.1	69	230 530
2A45							71.1	100	12.4	31.9	63	
2A63	120	1000	0	30	50	300	39.2	31	4.9	4.1	100	210 570
2A11							42.5	33	5.4	9.1	100	
2A12	80	1000	0	30	50	300	62.1	107	10.5	13.1	98	344 642
2A103	40	1000	0	30	50	300	88.4	580	48.8	73.	0	406 690

(a) ND - Not Determined; Specimen Failed in End Tab or Shoulder

TABLE 5-5. Task A. Quadratic Hydrogen Peroxide Design Cert Test Results

Specimen No.	Temp. (°C)	O ₂	Variable Levels (ppb)			CO ₂	Failure Time (h)	Maximum Breaking Stress		Time-to-Maximum Stress		RA (a) (%)	Fracture Mode		ECP (mV vs SHE)
			H ₂ O ₂	CL	SO ₄			(Ksi)	(h)	(%)	(h)		(SIGSCC) 304	Pt	
2A32	80	500	2000	30	50	300	87	51.6	74	ND	ND	ND	100	590	480
2A104							70	47.6	43	5.7		9.9	100		
2A67	80	275	2000	30	500	300	56	44.9	39	5.5		10.8	100	581	463
2A53							110	56.1	80	10.5		14.2	100		
2A70	80	195	2000	30	10	300	90	54.5	71	8.3		17.0	97	635	474
2A51							89	50.5	65	8.4		12.4	99		
2A36	80	500	5000	30	50	300	39	43.1	34	ND		ND	100	585	478
2A46							114	60.7	98	ND		ND	100		
2A54	80	100	400	30	50	300	83	47.0	51	7.7		14.0	100	635	478
2A27							54	39.7	34	4.8		13.8	99		
2A9	80	250	2000	100	50	300	69	39.8	30	6.8		3.5	100	645	481
2A43							34	41.8	32	ND		ND	100		
2A40	80	110	2000	2	50	300	220	73.2	212	ND		ND	ND	595	486
2A59							315	76.6	295	30.0		47.5	55		
2A8 ^(b)	80	700	5000	30	50	300	70	52.2	34	9.0		11.3	100	670	627
2A55							128	70.6	124	15.2		31.8	39		
2A41	80	210	2000	30	50	300	78	44.9		5.6		6.1	98	630	470

(a) ND - Not Determined; Specimen Failed in End Tab or Shoulder

(b) Repeat of 2A36/2A46

TABLE 5-6. Cert Test Results For Low Chloride/Sulphate Extension

Specimen No.	Temp. (°C)	Variable Levels (ppb)			Failure Time (h)	Maximum Breaking Stress		Time-to-Maximum Stress		RA Mode (X) (ZIGSCC)		Time-to-ECP (mV vs SHE) 304 Pt	
		H ₂ O ₂	CL ⁻	SO ₄ ⁼		(ksi)	(h)	(h)	(X)	(Z)	(X)	(h)	(h)
2A13	105	475	2000	2	17	300	127	55.8	102	11.3	22.0	98	605 488
2A14	105	390	2000	16.5	7.2	300	78	46.3	55	7.1	16.0	95	600 485
2A15	105	350	2000	7.4	7.2	300	132	60.9	107	12.0	26.9	80	557 502
2A16	105	340	2000	2	7.2	300	261	72.5	222	18.1	ND ^(a)	ND	590 544

(a) ND - Not determined; Shoulder or End Tab Failure

TABLE 5-7. Cor Test Results For Shield Water Environments

Specimen No.	Temp. (°C)	Variable Levels (ppb)		CO ₂	Failure Time		Maximum Time-to-Maximum Stress		RA (X) (XIGSCC)	Fracture Mode	ECP (mV vs SHE)
		H ₂ O ₂	CL ₂		(h)	(h)	(ksi)	(h)			
2A116	80	-	2000	50	73	43	45.1	5.8	-	-	-
2A125	80	-	2000	50	51	26	37.4	4.7	5.8	-	612 530
2A131	80	-	2000	2000	168	141	64.1	12.4	ND (a)	-	-
2A110	80	-	2000	2000	108	91	58.4	9.8	25.3	-	575 507
2A122(b)	80	-	2000	50	101	99	57.3	ND	ND	-	-
2A107(b)	80	-	2000	50	341	310	78.6	27.9	47.0	-	580 505

(a) ND - Not determined; Shoulder or End Tab Failure

(b) NO₃ - 3000 ppb (pH - 4.9 - 5.3)

TEST IDENTIFICATION				TEST CONDITIONS									
TEST SPECI- S SEQ				CODED AND PHYSICAL SCALES									
REF	COND	MEN NO.	L T IN	CL,		TEMP,		SO4,		OX,		CO2,	
D.	NO.	2A--	P A LP.	CLC	PPR	TEMPC	C	SO4C	PPR	OXC	PPR	CO2C	PPR
1	0 1	38	B 2 2	-1.0	8.2	-1.0	55	-1.0	17	-1.0	244	-1.0	82
2	0 2	98	A 1 5	-1.0	8.2	-1.0	55	-1.0	17	1.0	3755	1.0	683
3	0 3	64	D 5 1	-1.0	8.2	-1.0	55	1.0	187	-1.0	244	1.0	683
4	0 4	97	C 2 5	-1.0	8.2	-1.0	55	1.0	187	1.0	3755	-1.0	82
5	0 5	52	B 2 3	-1.0	8.2	1.0	105	-1.0	17	-1.0	244	1.0	683
6	0 6	47	C 2 4	-1.0	8.2	1.0	105	-1.0	17	1.0	3755	-1.0	82
7	0 7	29	C 2 2	-1.0	8.2	1.0	105	1.0	187	-1.0	244	-1.0	82
8	0 8	35	A 1 2	-1.0	8.2	1.0	105	1.0	187	1.0	3755	1.0	683
9	0 9	69	B 2 4	1.0	68	-1.0	55	-1.0	17	-1.0	244	1.0	683
10	010	105	A 1 6	1.0	68	-1.0	55	-1.0	17	1.0	3755	-1.0	82
11	011	26	A 2 1	1.0	68	-1.0	55	1.0	187	-1.0	244	-1.0	82
12	012	31	C 2 3	1.0	68	-1.0	55	1.0	187	1.0	3755	1.0	683
13	013	33	B 2 1	1.0	68	1.0	105	-1.0	17	-1.0	244	-1.0	82
14	014	50	A 1 4	1.0	68	1.0	105	-1.0	17	1.0	3755	1.0	683
15	015	49	A 1 3	1.0	68	1.0	105	1.0	187	-1.0	244	1.0	683
16	016	23	C 2 1	1.0	68	1.0	105	1.0	187	1.0	3755	-1.0	82

TEST IDENTIFICATION				TEST RESULTS									
TEST SPECI- S SEQ				TTF, TMS ATMS,				MAX STRESS,		ECP-SS FRAC			
REF	COND	MEN NO.	L T IN	TTF,	TMS	ATMS,				DUC-	MV,	SURF,	
D.	NO.	2A--	P A LP.	HRS	HRS	HRS	LATMS	KSI	ZEL	ZRA	ILITY	SHE	XIGSCC
1	0 1	38	B 2 2	374	336	361	2.5575	81.1	38.9	58.6	97.5	263	22
2	0 2	98	A 1 5	593	519	497	2.6964	81.9	47.8	66.8	114.6	391	0
3	0 3	64	D 5 1	321	460	455	2.6580	83.4	45.2	59.6	104.8	186	0
4	0 4	97	C 2 5	434	374	404	2.6064	82.3	40.3	64.8	105.1	390	3
5	0 5	52	B 2 3	121	66	65	1.8129	48.6	12.1	10.2	22.3	179	98
6	0 6	47	C 2 4	104	82	82	1.9138	55.0	9.5	15.4	24.9	301	100
7	0 7	29	C 2 2	57	30	31	1.4914	41.5	4.9	10.0	14.9	245	100
8	0 8	35	A 1 2	47	28	28	1.4472	41.1	2.6	6.4	9.0	276	100
9	0 9	69	B 2 4	495	443	455	2.6580	80.5	44.8	68.2	113.0	284	0
10	010	105	A 1 6	389	238	245	2.3892	76.3	40.0	60.0	100.0	342	ND
11	011	26	A 2 1	274	214	200	2.3010	96.1	24.1	26.6	50.7	219	67
12	012	31	C 2 3	484	414	439	2.6425	82.5	43.2	68.0	111.2	389	0
13	013	33	B 2 1	129	78	80	1.9031	57.6	11.5	17.0	28.5	183	87
14	014	50	A 1 4	72	48	50	1.6990	47.2	5.5	12.2	17.7	270	100
15	015	49	A 1 3	75	52	53	1.7243	47.6	5.3	9.9	15.2	206	100
16	016	23	C 2 1	52	34	34	1.5315	42.4	4.7	8.9	13.6	307	100

P = ENVIRONMENT CONTROL LOOP
 LC, ETC = CHLORIDE CONC, CODED SCALE
 TTF = TIME TO FAILURE
 ATMS = ADJUSTED TMS
 EL = PERCENT ELONGATION
 DUCTILITY = ZEL + ZRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION
 CL, ETC = CHLORIDE CONC, PHYSICAL SCALE
 TMS = TIME TO MAXIMUM STRESS
 LATMS = LOG-10 ATMS
 ZRA = PERCENT REDUCTION OF AREA
 ND = NOT DETERMINED

Table 5-8. Test Results: Oxygen Linear Design

TEST IDENTIFICATION					TEST CONDITIONS									
TEST SPECI- S SEQ					CODED AND PHYSICAL SCALES									
REF	COND	MEN	NO.	L T IN	CLC	CL,	TEMP,	SO4,	OX,					
NO.	NO.	2A--	P A LP.			PPR	TEMP C	SO4C	PPR	OXC	PPR	CO2C	PPR	
17	019	11	R 2 2	0.	30	1.6	120	0.	50	0.	1000	0.	300	
18	019	63	R 1 2	0.	30	1.6	120	0.	50	0.	1000	0.	300	
19	020	103	A 1 3	0.	30	-1.6	40	0.	50	0.	1000	0.	300	
20	021	48	A 1 1	0.	30	0.	80	1.6	500	0.	1000	0.	300	
21	021	90	A 2 1	0.	30	0.	80	1.6	500	0.	1000	0.	300	
22	022	60	R 2 1	0.	30	0.	80	-1.6	10	0.	1000	0.	300	
23	022	62	R 1 1	0.	30	0.	80	-1.6	10	0.	1000	0.	300	
24	023	10	C 1 2	0.	30	0.	80	0.	50	1.6	8000	0.	300	
25	023	39	C 2 2	0.	30	0.	80	0.	50	1.6	8000	0.	300	
26	024	44	A 1 2	0.	30	0.	80	0.	50	-1.6	100	0.	300	
27	024	45	A 2 2	0.	30	0.	80	0.	50	-1.6	100	0.	300	
28	027	28	C 1 1	0.	30	0.	80	0.	50	0.	1000	0.	300	
29	027	66	C 2 1	0.	30	0.	80	0.	50	0.	1000	0.	300	
30	027	12	R 1 3	0.	30	0.	80	0.	50	0.	1000	0.	300	

TEST IDENTIFICATION					TEST RESULTS									
TEST SPECI- S SEQ														
REF	COND	MEN	NO.	L T IN	TTF,	TMS	ATMS,	MAX				ECP-SS	FRAC	
NO.	NO.	2A--	P A LP.		HRS	HRS	HRS	LATMS	STRESS,	ZEL	ZRA	DUCT-	MV,	SURF,
									KSI			TILITY	SHE	ZIGSCC
17	019	11	R 2 2		55	33	34	1.5315	42.5	5.4	9.1	14.5	210	100
18	019	63	R 1 2		54	31	31	1.4914	39.2	4.9	4.1	9.0	210	100
19	020	103	A 1 3		616	580	555	2.7443	88.4	48.8	73.4	122.2	406	0
20	021	48	A 1 1		180	128	128	2.1072	67.6	14.5	21.8	36.3	287	69
21	021	90	A 2 1		210	164	170	2.2304	72.4	20.0	30.2	50.2	287	60
22	022	60	R 2 1		212	181	185	2.2672	76.1	20.0	30.0	50.0	315	ND
23	022	62	R 1 1		289	241	270	2.4314	75.4	27.8	53.6	81.4	315	30
24	023	10	C 1 2		233	211	209	2.3201	73.8	21.6	33.9	55.5	420	88
25	023	39	C 2 2		169	148	150	2.1761	67.5	15.6	28.8	44.4	420	8
26	024	44	A 1 2		140	107	110	2.0414	62.3	11.3	28.1	39.4	230	69
27	024	45	A 2 2		128	100	110	2.0414	71.1	12.4	31.9	44.3	230	63
28	027	28	C 1 1		123	111	102	2.0086	58.8	7.7	11.6	19.3	313	ND
29	027	66	C 2 1		137	95	94	1.9731	56.3	12.4	18.6	31.0	313	100
30	027	12	R 1 3		135	106	102	2.0086	62.1	10.5	13.1	23.6	344	98

LP = ENVIRONMENT CONTROL LOOP
 CLC, ETC = CHLORIDE CONC, CODED SCALE
 TTF = TIME TO FAILURE
 ATMS = ADJUSTED TMS
 ZEL = PERCENT ELONGATION
 DUCTILITY = ZEL + ZRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION
 CL, ETC = CHLORIDE CONC, PHYSICAL SCALE
 TMS = TIME TO MAXIMUM STRESS
 LATMS = LOG-10 ATMS
 ZRA = PERCENT REDUCTION OF AREA
 ND = NOT DETERMINED

Table 5-9. Test Results: Oxygen Quadratic Design

TEST IDENTIFICATION					TEST CONDITIONS									
TEST SPECI- S SEQ					CODED AND PHYSICAL SCALES									
REF NO.	COND NO.	MEN NO.	L T IN	CLC	CL, PPR	TEMP, °C	SO4C	SO4, PPR	PEROX, PPR	PEROX, PPR	CO2, PPR	CO2, PPR	OPS CODED	O2 PPR
1	P 1	24	D 5 2	-1.0	8.2	-1.0	55 -1.0	17 -1.0	845 -1.0	82	-1.911	62		
2	P 2	56	D 5 4	-1.0	8.2	-1.0	55 -1.0	17 1.0	3703 1.0	683	-1.431	129		
3	P 3	42	B 2 3	-1.0	8.2	-1.0	55 1.0	187 -1.0	845 1.0	683	-1.479	120		
4	P 4	37	C 1 5	-1.0	8.2	-1.0	55 1.0	187 1.0	3703 -1.0	82	0.348	1600		
5	P 5	61	D 5 3	-1.0	8.2	1.0	105 -1.0	17 -1.0	845 1.0	683	-1.943	59		
6	P 6	34	D 5 5	-1.0	8.2	1.0	105 -1.0	17 1.0	3703 -1.0	82	-1.426	130		
7	P 7	7	C 2 1	-1.0	8.2	1.0	105 1.0	187 -1.0	845 -1.0	82	-0.370	600		
8	P 8	57	B 2 2	-1.0	8.2	1.0	105 1.0	187 1.0	3703 1.0	683	0.348	1600		
9	P 9	30	D 5 1	1.0	68	-1.0	55 -1.0	17 -1.0	845 1.0	683	-2.088	47		
10	P10	65	C 2 4	1.0	68	-1.0	55 -1.0	17 1.0	3703 -1.0	82	0.371	1650		
11	P11	25	A 1 1	1.0	68	-1.0	55 1.0	187 -1.0	845 -1.0	82	-0.500	500		
12	P12	58	C 2 2	1.0	68	-1.0	55 1.0	187 1.0	3703 1.0	683	0.	1000		
13	P13	68	B 2 1	1.0	68	1.0	105 -1.0	17 -1.0	845 -1.0	82	-0.574	450		
14	P14	102	A 1 4	1.0	68	1.0	105 -1.0	17 1.0	3703 1.0	683	0.589	2200		
15	P15	99	C 2 3	1.0	68	1.0	105 1.0	187 -1.0	845 1.0	683	-0.163	800		
16	P16	101	A 1 2	1.0	68	1.0	105 1.0	187 1.0	3703 -1.0	82	0.477	1900		

TEST IDENTIFICATION					TEST RESULTS									
TEST SPECI- S SEQ					MAX STRESS, DUC- MV, FRAC									
REF NO.	COND NO.	MEN NO.	L T IN	CLC	TTF, HRS	TMS, HRS	ATMS, HRS	LATMS	KSI	ZEL	XRA*	TILITY	MOV, SHE	FRAC SURF, ZIGSCC
1	P 1	24	D 5 2		500	460	440	2.6435	81.6	56.4	46.2	102.6	444	0
2	P 2	56	D 5 4		526	417	430	2.6335	82.7	47.9	60.3	108.2	577	0
3	P 3	42	B 2 3		455	347	340	2.5315	81.5	30.4	<u>45.6</u>	76.0	620	ND
4	P 4	37	C 1 5		472	454	465	2.6675	81.5	47.1	<u>67.5</u>	114.6	685	0
5	P 5	61	D 5 3		202	178	182	2.2601	68.4	22.7	32.8	55.5	473	74
6	P 6	34	D 5 5		187	142	139	2.1430	62.7	15.7	<u>23.6</u>	39.3	489	100
7	P 7	7	C 2 1		56	36	36	1.5563	41.4	6.0	8.4	14.4	580	100
8	P 8	57	B 2 2		26	20	20	1.3010	35.5	2.0	3.1	5.1	525	100
9	P 9	30	D 5 1		144	128	131	2.1173	68.7	15.9	22.8	38.7	450	72
10	P10	65	C 2 4		107	73	75	1.8751	57.1	9.8	20.3	30.1	672	95
11	P11	25	A 1 1		207	182	178	2.2504	70.6	16.5	<u>24.8</u>	41.3	645	ND
12	P12	58	C 2 2		301	178	180	2.2553	70.2	14.7	<u>22.1</u>	36.8	670	ND
13	P13	68	B 2 1		58	38	38	1.5798	45.9	4.4	4.5	8.9	512	100
14	P14	102	A 1 4		41	20	20	1.3010	35.4	4.0	2.9	6.9	593	100
15	P15	99	C 2 3		36	22	22	1.3424	36.1	2.6	3.3	5.9	588	100
16	P16	101	A 1 2		34	16	16	1.2041	34.2	3.6	2.4	6.0	651	100

* = ENVIRONMENT CONTROL LOOP
 CLC, ETC = CHLORIDE CONC, CODED SCALE
 TTF = TIME TO FAILURE
 TMS = ADJUSTED TMS
 ZEL = PERCENT ELONGATION
 DUCTILITY = ZEL + XRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION
 CL, ETC = CHLORIDE CONC, PHYSICAL SCALE
 TMS = TIME TO MAXIMUM STRESS
 LATMS = LOG-10 ATMS
 XRA = PERCENT REDUCTION OF AREA
 ND = NOT DETERMINED

* INTERSCORED VALUES ARE FROM SPECIMENS WHICH FAILED IN THE SHOULDER OR END TAB SUCH THAT XRA COULD NOT BE MEASURED. THE 'IMPLIED' VALUE SHOWN WAS TAKEN AS 1.5 X ZEL, THE AVERAGE RATIO.

Table 5-10. Test Results: Hydrogen Peroxide Linear Design

TEST IDENTIFICATION					TEST CONDITIONS									
TEST SPECI- S SED					CODED AND PHYSICAL SCALES									
REF NO.	COND NO.	REN NO.	L T IN	P A LP.	CLC	CL, PPB	TEMP, C	SO4C	SO4, PPB	PEROX, PPB	CO2C	CO2, PPB	OPS CODED	O2 PPB
17	P17	9	C 1 3		1.6	100	0.	80	0.	50	0.	2000	0.	300
18	P17	43	C 2 3		1.6	100	0.	80	0.	50	0.	2000	0.	300
19	P18	40	B 1 4		-1.6	2	0.	80	0.	50	0.	2000	0.	300
20	P18	59	B 2 4		-1.6	2	0.	80	0.	50	0.	2000	0.	300
21	P21	53	B 2 2		0.	30	0.	80	1.6	500	0.	2000	0.	300
22	P21	67	B 1 2		0.	30	0.	80	1.6	500	0.	2000	0.	300
23	P22	51	C 2 1		0.	30	0.	80	-1.6	10	0.	2000	0.	300
24	P22	70	C 1 1		0.	30	0.	80	-1.6	10	0.	2000	0.	300
25	P23	36	B 1 3		0.	30	0.	80	0.	50	1.6	5000	0.	300
26	P23	46	B 2 3		0.	30	0.	80	0.	50	1.6	5000	0.	300
27	P24	54	C 1 2		0.	30	0.	80	0.	50	-1.6	400	0.	300
28	P24	27	C 2 2		0.	30	0.	80	0.	50	-1.6	400	0.	300
29	P27	32	B 1 1		0.	30	0.	80	0.	50	0.	2000	0.	300
30	P27	104	B 2 1		0.	30	0.	80	0.	50	0.	2000	0.	300
31	P23	8	A 1 1		0.	30	0.	80	0.	50	1.6	5000	0.	300
32	P23	55	A 2 1		0.	30	0.	80	0.	50	1.6	5000	0.	300
33	P27	41	C 1 4		0.	30	0.	80	0.	50	0.	2000	0.	300

TEST IDENTIFICATION					TEST RESULTS									
TEST SPECI- S SED					MAX STRESS, DUC- ECP-SS FRAC									
REF NO.	COND NO.	REN NO.	L T IN	P A LP.	TTF, HRS	TMS HRS	ATHS, HRS	LATHS	STRESS, KSI	ZEL*	ZRA*	DUCTILITY	MV, SHE	SURF, ZIGSCC
17	P17	9	C 1 3		69	30	30	1.4771	39.8	6.8	3.5	10.3	645	100
18	P17	43	C 2 3		34	32	32	1.5051	41.8	4.0	4.0	10.0	645	100
19	P18	40	B 1 4		220	212	215	2.3324	73.2	22.8	34.2	57.0	595	ND
20	P18	59	B 2 4		315	295	297	2.4728	76.6	30.0	47.5	77.5	595	55
21	P21	53	B 2 2		110	80	79	1.8974	56.1	10.5	14.2	24.7	581	100
22	P21	67	B 1 2		56	39	40	1.4021	44.9	5.5	10.8	14.3	581	100
23	P22	51	C 2 1		89	65	63	1.7993	50.5	8.4	12.4	20.8	635	99
24	P22	70	C 1 1		90	71	71	1.8513	54.5	8.3	17.0	25.3	635	97
25	P23	36	B 1 3		39	34	34	1.5315	43.1	4.4	6.6	11.0	585	100
26	P23	46	B 2 3		114	98	98	1.9912	60.7	12.8	19.2	32.0	585	100
27	P24	54	C 1 2		83	51	52	1.7160	47.0	7.7	14.0	21.7	635	100
28	P24	27	C 2 2		54	34	35	1.5441	39.7	4.8	13.8	18.6	635	99
29	P27	32	B 1 1		87	74	72	1.8573	51.6	9.8	14.7	24.5	590	100
30	P27	104	B 2 1		74	43	43	1.6335	47.6	5.7	9.9	15.6	590	100
31	P23	8	A 1 1		70	34	34	1.5563	52.2	9.0	11.3	20.3	670	100
32	P23	55	A 2 1		128	124	133	2.1239	70.6	15.2	31.8	47.0	670	39
33	P27	41	C 1 4		78	49	47	1.6721	44.9	5.6	6.1	11.7	630	98

LP = ENVIRONMENT CONTROL LOOP
 CLC, ETC = CHLORIDE CONC, CODED SCALE
 TTF = TIME TO FAILURE
 ATHS = ADJUSTED TMS
 ZEL = PERCENT ELONGATION
 DUCTILITY = ZEL + ZRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION
 CL, ETC = CHLORIDE CONC, PHYSICAL SCALE
 TMS = TIME TO MAXIMUM STRESS
 LATHS = LOG-10 ATHS
 ZRA = PERCENT REDUCTION OF AREA
 ND = NOT DETERMINED

* UNDERScoreD VALUES UNDER BOTH ZEL AND ZRA ARE FROM SPECIMENS WHICH FAILED IN THE SHOULDER OR END TAB SUCH THAT NEITHER PARAMETER COULD BE MEASURED. THE 'IMPLIED' VALUES ENTERED ARE BASED ON THE OBSERVED TMS AND THE 'DUCTILITY' CURVE IN FIGURE 5-12, SUCH THAT ZEL = (1/2.5)DUCTILITY AND ZRA = (1.5/2.5)DUCTILITY.

Table 5-11. Test Results: Hydrogen Peroxide Quadratic Design

TEST IDENTIFICATION						TEST CONDITIONS CODED AND PHYSICAL SCALES										
REF NO.	COND NO.	MEN NO.	L T IN	S SEQ	CLC	CL, PPB	TEMP, TEMPC	C	SO4C	SO4, PPB	PEROX, PEROXC	PPB	CO2C	CO2, PPB	OPS CODED	O2 PPB
1	P48	13	C 1 2		-1.600	2	1.0	105	-1.0	17	0.	2000	0.	300	-0.536	475
2	P50	14	C 1 1		-0.533	16.5	1.0	105	-2.0	7.2	0.	2000	0.	300	-0.675	390
3	P51	15	R 1 1		-1.067	7.4	1.0	105	-2.0	7.2	0.	2000	0.	300	-0.751	350
4	P52	16	A 1 1		-1.600	2	1.0	105	-2.0	7.2	0.	2000	0.	300	-0.771	340

TEST IDENTIFICATION						TEST RESULTS								
REF NO.	COND NO.	MEN NO.	L T IN	S SEQ	TTF, HRS	TMS HRS	ATMS, HRS	MAX STRESS, LATMS	KSI	ZEL	ZRA*	DUCT- ILITY	ECF-SS MV, SHE	FRAC SURF, XIGSCC
1	P48	13	C 1 2		127	102	101	2.0043	55.8	11.3	22.0	33.3	605	98
2	P50	14	C 1 1		78	55	55	1.7404	46.3	7.1	16.0	23.1	600	95
3	P51	15	R 1 1		132	107	110	2.0414	60.9	12.0	26.9	38.9	557	80
4	P52	16	A 1 1		261	222	207	2.3160	72.5	18.1	<u>27.1</u>	45.2	590	ND

LP = ENVIRONMENT CONTROL LOOP

CLC, ETC = CHLORIDE CONC, CODED SCALE

TTF = TIME TO FAILURE

ATMS = ADJUSTED TMS

ZEL = PERCENT ELONGATION

DUCTILITY = ZEL + ZRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION

CL, ETC = CHLORIDE CONC, PHYSICAL SCALE

TMS = TIME TO MAXIMUM STRESS

LATMS = LOG-10 ATMS

ZRA = PERCENT REDUCTION OF AREA

ND = NOT DETERMINED

* THE UNDERScoreD VALUE IS FROM A SPECIMEN WHICH FAILED IN THE SHOULDER SUCH THAT ZRA COULD NOT BE MEASURED. THE 'IMPLIED' VALUE SHOWN WAS TAKEN AS 1.5 X ZEL, THE AVERAGE RATIO.

Table 5-12. Test Results: Low Chloride-Sulphate Test Extension

TEST IDENTIFICATION										TEST CONDITIONS										ENVOX BY	
TEST SPECI-			S SEQ		CODED AND PHYSICAL SCALES										Perox	Oxygen	Gas Add	SOC.			
REF NO.	COND NO.	MEN NO.	L T IN	CL,	TEMP,	S04,	PEROX,	CO2,	ORS O2												
NO.	NO.	2A--	P A LP.	CLC PPB	TEMPC C	S04C	PEROXC PPB	CO2C	PPB	CODED	PPB	PPB	PPB	PPB	PPB	PPB	PPB				
1W	1	20	A 1 1	-1.6 2	-1.8 35	-2.751 4	-1.6 400	-1.6 20	-1.600 100												
2W	2	21	A 2 1	-1.6 2	-1.8 35	-2.751 4	-1.6 400	-1.6 20	-1.600 100												
3W	3	22	B 1 1	0. 30	0.8 100	0. 50	0. 2000	0. 300	0. 1000												
4W	4	94	B 2 1	0. 30	0.8 100	0. 50	0. 2000	0. 300	0. 1000												
5F	5	18	B 1 2	0. 30	0.8 100	0. 50	0. 2000	0. 300	0. 1000												
6F	6	19	B 2 2	0. 30	0.8 100	0. 50	0. 2000	0. 300	0. 1000												
7W	7	95	C 1 1	1.6 100	1.6 120	1.600 500	1.6 5000	1.6 1000	1.600 8000												
8W	8	96	C 2 1	1.6 100	1.6 120	1.600 500	1.6 5000	1.6 1000	1.600 8000												
9F	9	17	C 2 2	-1.6 2	1.6 120	-2.751 4	-1.6 400	-1.6 20	-1.600 100												
10F	10	91	A 1 2	1.6 100	-1.8 35	1.600 500	1.6 5000	1.6 1000	1.600 8000												
11F	11	92	B 2 3	0. 30	0. 80	0. 50	0. 2000	0. 300	-0.259 700												
12F	12	93	C 2 3	0. 30	0. 80	0. 50	-- --	0. 300	-0.259 700												

TEST IDENTIFICATION										TEST RESULTS						ECP-SS		FRAC
TEST SPECI-				S SEQ					MAX				DUC-	MV,	FRAC			
REF	COND	MEN	NO.	L T IN	TTF,	TMS	ATMS,		STRESS,						SURF,			
NO.	NO.	2A--	P A LP.		HRS	HRS	HRS	LATMS	KSI	ZEL	ZRA	TILITY	SHE	ZIGSCC				
1W	1	20	A 1 1		386	386	470	2.6721	91.7	56.6	71.5	128.1	400	0				
2W	2	21	A 2 1		386	385	480	2.6812	100.2	59.9	71.0	130.9	400	0				
3W	3	22	B 1 1		55	37	37	1.5682	41.9	6.4	8.0	14.4	560	92				
4W	4	94	B 2 1		52	34	34	1.5315	44.4	3.7	2.3	6.0	560	100				
5F	5	18	B 1 2		50	33	33	1.5185	44.5	3.8	7.8	11.6	560	100				
6F	6	19	B 2 2		50	27	28	1.4472	50.3	4.1	4.0	8.1	560	100				
7W	7	95	C 1 1		38	30	29	1.4624	34.6	2.5	4.3	6.8	520	100				
8W	8	96	C 2 1		30	20	20	1.3010	31.3	2.4	3.3	5.7	520	100				
9F	9	17	C 2 2		115	84	84	1.9243	51.0	10.7	19.7	30.4	515	89				
10F	10	91	A 1 2		361	361	425	2.6284	90.8	53.3	63.5	116.8	600	0				
11F	11	92	B 2 3		81	55	55	1.7404	48.9	7.4	12.6	20.0	575	98				
12F	12	93	C 2 3		140	111	111	2.0453	57.8	12.6	24.4	37.0	307	94				

LP = ENVIRONMENT CONTROL LOOP

CLC, ETC = CHLORIDE CONC, CODED SCALE

TTF = TIME TO FAILURE

ATMS = ADJUSTED TMS

ZEL = PERCENT ELONGATION

DUCTILITY = ZEL + ZRA

STA = TENSILE MACHINE AND AUTOCLAVE STATION

CL, ETC = CHLORIDE CONC, PHYSICAL SCALE

TMS = TIME TO MAXIMUM STRESS

LATMS = LOG-10 ATMS

ZRA = PERCENT REDUCTION OF AREA

UNDER REF. NO., 'W' = HEAT TREATMENT TO SIMULATE WELD SENSITIZATION, 15 HOURS AT 600 C
'F' = HEAT TREATMENT BY FURNACE SENSITIZATION, 24 HOURS AT 600 C

FOR TEST CONDITIONS 1, 2 AND 10, SPECIMEN WAS PULLED TO FAILURE AT TTF HOURS SHOWN;
ATMS HOURS ARE GREATER.

Table 5-13. Test Results: Option 1 Hydrogen Peroxide and Oxygen Environments

Column	Adopted Oxygen Model		Adopted Peroxide Model			
Model Name	A	B	C	D	E	
	Oxygen Linear	Oxygen Lin and Quad	Peroxide Linear	Peroxide Lin and Quad	Peroxide Lin, Quad and Low Cl-SO ₄	
No. of data	16	30	16	33	37	
R ²	0.954	0.936	0.950	0.863	0.829	
Std dev of resid	0.120	0.113	0.136	0.169	0.183	
Model Terms, Coded Scales	Intercept	2.127	2.085	1.437	1.791	1.811
	CLC	—	—	—	—	—
	TEMPC	-0.437	-0.417	-0.196	-0.231	-0.237
	SO4C	31.1	32.1	163	106	90
	TEMPC x SO4C	6.5	9.8	—	—	—
	TEMPC x CO2C	4.7	5.3	—	—	—
	CLC x SO4C	4.0	4.5	—	—	—
	(CLC) ²	—	—	—	—	—
(SO4C) ²	—	+0.0583	—	+0.0704	+0.0661	
Degrees of Freedom, df	11	24	11	27	31	
Critical F, F _{0.90:1,df}	3.23	2.93	3.23	2.90	2.88	
Reference Case	1	2	3.1	4.1	9	
Plotted in Figure No.		5-15		5-20	5-21A,B	

Table 5-14. Quality of Fit and Coefficients in Adopted Oxygen and Hydrogen Peroxide Models

Model Part (used for illustration)

Definition
Statistical Properties

$-0.0651 \times \text{TEMPC} \times \text{SO4C}$

Equation Term

None used.

-0.0651

Coefficient

A random variable whose value is estimated from the test data using the multiple regression method. Accordingly, the estimated value can be used in a test of significance (as to its difference from a true coefficient value of 0), in setting confidence limits if desired, etc. Use will be made of the phrasing, "This coefficient estimate was found to be significant (or not significant), at the 10% level." The phrase, "The effect of temperature is significant," is used in the same sense as "The coefficient estimate is significant."

TEMPC and SO4C

Each is a variable, or a physical variable.

An objective of this task is to identify each variable which has an effect on IGSCC; that is, when the value of the variable is changed, there is a marked change in IGSCC susceptibility, measured in this testing by a change in LATMS. As will be described in section 5.3.2.3, some variable X1 may cause this effect over only a particular range of another variable X2. X1 will be said to be "important over X2 from A to B". See also "Total slope", below.

$\text{TEMPC} \times \text{SO4C}$

Term

None used.

$- 0.0688 - 0.0651 \times \text{TEMPC} + 2 \times 0.0583 \times \text{SO4C}$

Total slope of LATMS over SO4C, $\partial \text{LATMS} / \partial \text{SO4C}$

Total slope is an estimate, and is a random variable since it is a function of other random variables. Pairs of values of TEMPC and SO4C will define a region where this total slope is significant; in the remaining region of TEMPC and SO4C pairs it is not significant. For the region of significance, the variable SO4C is said herein to be "important".

In Equation (5-1), 2.085 is the "Intercept"; it is the value of LATMS where all independent variables are 0. It differs only slightly from the mean LATMS due to near symmetry of the design, and to the presence of the quadratic term. All principles in this table apply to Equations (5-2), (5-13) and (5-14) as well.

Table 5-15. Definitions and Statistical Properties of Individual Parts of Equation (5-1)

Variable, X_1	Terms in model involving this variable	Total slope of LATMS over this variable, $\partial \text{LATMS} / \partial X_1$	Variance of total slope, $s_{\partial \text{LATMS} / \partial X_1}^2$
TEMPC			
x	x	$-0.417 \times \text{TEMPC} - 0.0651 \times \text{TEMPC} \times \text{SO4C} - 0.0598 \times \text{TEMPC} \times \text{CO2C}$	
	x	$-0.417 - 0.0651 \times \text{SO4C} - 0.0598 \times \text{CO2C}$	
	x	$(0.02275^2)^* + 0.02757^2 \times \text{SO4C}^2 + 0.02757^2 \times \text{CO2C}^2$	
SO4C			
x	x	$-0.0688 \times \text{SO4C} - 0.0651 \times \text{TEMPC} \times \text{SO4C} + 0.0583 \times \text{SO4C}^2$	
	x	$-0.0688 - 0.0651 \times \text{TEMPC} + 2 \times 0.0583 \times \text{SO4C}$	
	x	$0.02153^2 + 0.02757^2 \times \text{TEMPC}^2 + 4 \times 0.02518^2 \times \text{SO4C}^2$	
CO2C			
x	x	$(0. \times \text{CO2C})^{**} - 0.0598 \times \text{TEMPC} \times \text{CO2C}$	
	x	$(0.) - 0.0598 \times \text{TEMPC}$	
	x	$0.02757^2 + 0.02757^2 \times \text{TEMPC}^2$	

Model is Equation (5-1).

- * (0.02275^2) is $s_{-0.417}^2$, the variance of the coefficient estimate -0.417.
- ** Coefficient is not significant, but the variance was used.

Number of data 30 Degrees of freedom, $n-k-1$ 24 $t_{0.95, df}$ 1.711

90% confidence interval, upper limit (+) = $\partial \text{LATMS} / \partial X_1 \pm t_{0.95, df} s_{\partial \text{LATMS} / \partial X_1}$
lower limit (-)

Table 5-16 . Derivation of Lower and Upper 90% Confidence Limits for Total Slope of LATMS over each Variable in the Adopted Oxygen Model

Variable, X_1	Terms in model involving this variable	Total slope of LATMS over this variable, $\partial \text{LATMS} / \partial X_1$	Variance of total slope, $s_{\partial \text{LATMS} / \partial X_1}^2$
CLC			
x		$-0.237 \times \text{CLC} + 0.0661 \times \text{CLC} \times \text{SO}_4\text{C} + 0.0787 \times \text{CLC}^2$	
x		$-0.237 + 0.0661 \times \text{SO}_4\text{C} + 2 \times 0.0787 \times \text{CLC}$	
x		$(0.0343)^2 + 0.0374 \times \text{SO}_4\text{C}^2 + 4 \times 0.0363 \times \text{CLC}^2$	
TEMPC			
x		$-0.418 \times \text{TEMPC} - 0.107 \times \text{TEMPC} \times \text{SO}_4\text{C}$	
x		$-0.418 - 0.107 \times \text{SO}_4\text{C}$	
x		$0.0439^2 + 0.0393 \times \text{SO}_4\text{C}^2$	
SO ₄ C			
x		$(0. \times \text{SO}_4\text{C})^{**} - 0.107 \times \text{TEMPC} \times \text{SO}_4\text{C} + 0.0661 \times \text{CLC} \times \text{SO}_4\text{C}$	
x		$(0.) - 0.107 \times \text{TEMPC} + 0.0661 \times \text{CLC}$	
x		$0.0331^2 + 0.0393 \times \text{TEMPC}^2 + 0.0374 \times \text{CLC}^2$	

Model is Equation (5-13).

* (0.0343^2) is $s_{-0.237}^2$, the variance of the coefficient estimate -0.237.

** Coefficient is not significant, but the variance was used.

Number of data 37 Degrees of freedom, $n-k-1$ 31 $t_{0.95,df}$ 1.696

90% conf int on $\partial \text{LATMS} / \partial X_1$ upper lim (+) = $\partial \text{LATMS} / \partial X_1 \pm t_{0.95,df} s_{\partial \text{LATMS} / \partial X_1}$
lower lim (-)

Table 5-17 . Derivation of Lower and Upper 90% Confidence Limits for Total Slope of LATMS over each Variable in the Adopted Hydrogen Peroxide Model

The function, ΔLATMS = Adopted Hydrogen Peroxide Model - Adopted Oxygen Model

$$= 1.811 - 0.237 \times \text{CLC} - 0.418 \times \text{TEMPC} - 0.107 \times \text{TEMPC} \times \text{S04C} + 0.0661 \times \text{CLC} \times \text{S04C} + 0.0787 \times (\text{CLC})^2 \\ - (2.085 - 0.417 \times \text{TEMPC} - 0.0688 \times \text{S04C} - 0.0651 \times \text{TEMPC} \times \text{S04C} - 0.0598 \times \text{TEMPC} \times \text{C02C} + 0.0583 \times (\text{S04C})^2)$$

The variance of the function, $s_{\Delta\text{LATMS}}^2$, by propagation of errors

$$= 0.1829^2/37 + 0.0343^2 \times \text{CLC}^2 + 0.0439^2 \times \text{TEMPC}^2 + 0.0393^2 \times \text{TEMPC}^2 \times \text{S04C}^2 + 0.0374^2 \times \text{CLC}^2 \times \text{S04C}^2 + 0.0363^2 \times \text{CLC}^4 \\ + 0.1128^2/30 + 0.0233^2 \times \text{TEMPC}^2 + 0.0220^2 \times \text{S04C}^2 + 0.0282^2 \times \text{TEMPC}^2 \times \text{S04C}^2 + 0.0282^2 \times \text{TEMPC}^2 \times \text{C02C}^2 + 0.0258^2 \times \text{S04C}^4$$

Take degrees of freedom as the average of the two models, $(24 + 31)/2 = 27$; $t_{0.95,27} = 1.70$.

Calculate $90\% \text{CI, UL} = \Delta\text{LATMS} + t_{0.95,27} s_{\Delta\text{LATMS}}$.

Table 5-18. Derivation of 90% Confidence Interval, Upper Limit, for ΔLATMS

Figure 5-1. Option 1 CERT Test Results

2A95

2A96

(a) Variable High Levels (TTF = 30h)

2A20

2A21

(b) Variable Low Levels (TTF = 386h)

Figure 5-2. CERT Specimens after Testing in: (a) Variable High Levels and, (b) Variable Low Levels (Macrophotograph).

(a) 25X

(b) 100X

Figure 5-5. Fracture surface of Specimen J496 (ERI) Tested in Variable High Level Environment (SEM).

(a) 40X

(b) 210X

Figure 5-4. Fracture Surface of Specimen 2A21 CERT Tested in Variable Low Level Environment (SEM).

(a) 2A95-WS High Level Environment (120°C)

(b) 2A17-FS Low Level Environment (120°C)

Figure 5-5. IGSCC in CERT Specimens Tested at 120°C in: (a) High, and
(b) Low Level Environments (40X, Oxalic Acid Etch).

Figure 5-6. Load-Time Curves for Option 1
CERT Specimens Tested in
Various Environments

Figure 5-7. ECP vs Time for Loop C Showing Rapid Response and Sensitivity to Increase in HNO_3 Concentration

Figure 5-8. ECP vs Time for Loop B Showing Rapid Response and Sensitivity to the Addition of H_2O_2

HYDROGEN PEROXIDE RANGE: 960 - 5600 ppb

Figure 5-9. Hydrogen Peroxide-Oxygen-Temperature Relationship.

ELECTROCHEMICAL
POTENTIAL RANGE
(V SHE)

600
500
400
300
200
100

Figure 5-10. Range of Electrochemical Potentials
Measured at SRL Compared to GE Laboratories

Figure 5-11. Temperature Dependence of ECP's Measured at Various Oxygen - Hydrogen Peroxide Concentrations.

Figure 5-14. Relationship of Log Time to Failure to Log Adjusted Time to Maximum Stress

Figure 5-15. Test Results and Fitted Model for the Oxygen Designs (Adopted Oxygen Model) (Sheet 1 of 2)

SYMBOLS

Observed Values

Oxygen Linear Design, Table 4-6

Corner Points, 01-016: CLC = ± 1 , TEMPC = ± 1 , SO4C = ± 1 in combinations

	-1	+1
OXC	⊗	○
CO2C	⊖	○

Oxygen Quadratic Design, Table 4-7

Star Points, six in 017-026: One var at ± 1.6 , other four var at 0

	-1.6	+1.6
TEMPC	020 ▽	019 ▽
SO4C	022 ▽	021 ▽
OXC	024 ▽	023 ▽

Center Point, 027: All five variables at 0 ▽

Predicted Values, model in Table 5-148 and Equations (5-1) and (5-2)

At TEMPC = ± 1 and OXC = ± 1 , over CLC and SO4C at ± 1 :

CO2C = -1 ——— CO2C = +1 ———

At CLC = TEMPC = OXC = CO2C = 0, over SO4C: — — — — —

At TEMPC = -1.6, -1, 0, +1 and +1.6, all four other variables = 0: — — — — —

Figure 5-15. Test Results and Fitted Model for the Oxygen Designs
(Adopted Oxygen Model) (Sheet 2 of 2)

Figure 5-16. Confidence Limits on $\partial Y / \partial X_1$ for a Surface where the X_2 Test Data and Operating Region is in the Region where X_2 is Important

Figure 5-17. In Adopted Oxygen Model, Region of Importance of TEMPC

Figure 5-18. In Adopted Oxygen Model, Region of Importance of S04C

Figure 5-19. In Adopted Oxygen Model, Regions of Importance of CO2C

Figure 5-20. Test Results and Fitted Model for the Peroxide Designs (Sheet 1 of 2)

SYMBOLS

Observed Values

Peroxide Linear Design, Table 4-6

Corner Points, P1-P16: CLC = ± 1 , TEMPC = ± 1 , SO4C = ± 1 in combinations

	-1	+1
PEROXC
CO2C

Peroxide Quadratic Design, Table 4-7

Star Points, P17-P18 and P21-P24: One variable at ± 1.6 , other four variables at 0

	-1.6	+1.6
CLC	P18	P17
SO4C	P22	P21
PEROXC	P24	P23

Center Point, P27: All five variables at 0

Low Chloride-Sulphate Test Extension, Table 4-8, Points P48, P50-P52:

Predicted Values, model in Table 5-14E and Equations (5-1) and (5-2)

At TEMPC = -1, PEROXC and CO2C = ± 1 , over CLC and SO4C at ± 1 :

At TEMPC = 0, PEROXC and CO2C = ± 1 , over CLC and SO4C at 0:

At TEMPC = +1, PEROXC and CO2C = ± 1 , over CLC and SO4C at ± 1 :

Figure 5-20. Test Results and Fitted Model for the Peroxide Designs
(Sheet 2 of 2)

Figure 5-21. Test Results and Fitted Model for the Peroxide Designs and
the Low Chloride-Sulphate Test Extension (Adopted Peroxide
Model) (Sheet 2 of 2)

Figure 5-23. Comparison of Predictions by Adopted Oxygen and Peroxide Models

Figure 5-24. In Adopted Peroxide Model, Region of Importance of CLC

Figure 5-25. In Adopted Peroxide Model, Region of Importance of S04C

Figure 5-26. Test Results and Values Predicted by the Adopted Hydrogen Peroxide Model, for Option 1 Testing

Figure 5-27. Relationship of Concentration of Oxygen by Dissociation to Peroxide Concentration

Figure 5-28. Relationship of ECP-SS to Log Adjusted Time to Maximum Stress, Oxygen Designs

Data from the Peroxide Linear and Quadratic Designs, and the Low Chloride-Sulphate Test Extension, are shown.

6.0 SUMMARY, FULFILLMENT OF OBJECTIVES AND CONCLUSIONS

6.1 Summary

Over 80 CERT tests were performed in environments simulating SRP reactors (except irradiation). Environmental simulation was made possible by construction of special water circulation modules which allowed independent control of the variables: chloride, temperature, sulphate, oxygen, hydrogen peroxide, carbon dioxide and nitrate. Coupling these modules to a specially constructed chemical analysis module, and to an IBM-PC/Keithley data acquisition system, allowed real-time monitoring and recording of environment parameters as well as CERT test parameters and results. An example of the environment control using real-time monitoring is given in Appendix B; the control of variables relative to established tolerance bands is illustrated.

The ECP of Type 304 stainless steel was monitored during each CERT test. When hydrogen peroxide was present in the environment, typical ECP values were in the range +450 to +700 mV(SHE). These values are in good agreement with the range of values observed in SRP reactors as shown in Figure 5-10. Thus, the test environments were comparable to the plant environment electrochemically. Based on BWR experience, the highly positive ECPs means that the tests were conducted in environmental regimes where IGSCC is predominant; this was verified by test results. When hydrogen peroxide was removed from the environment the ECP range decreased by about 350 mV(SHE) as shown in Figure 5-10. This reveals the strong oxidizing power of

hydrogen peroxide. As shown in Figure 5-11, average ECP values increased as the oxidizing power of the environment increased either by increased oxygen alone or by combinations of increased amounts of oxygen and hydrogen peroxide, but these ECP changes per se had no effect on IGSCC as indicated by the CERT tests.

Prior to starting a statistical study of the effect of environment variables on IGSCC of Type 304 stainless steel, 12 CERT tests were completed under Option 1. These were very important tests for several reasons. First, they verified that IGSCC occurred over a wide range of simulated SRP environments as shown in Figure 5-1. Temperature was found to have a strong effect, IGSCC did not occur at 35°C but was observed at temperatures in the range 78° to 120°C. Fracture surfaces of specimens ranged from 100% ductile to 100% IGSCC (Figures 5-3 to 5-5). Second, they showed that the presence of hydrogen peroxide increased IGSCC at 78°C. Third, they showed that a considerable amount of oxygen was produced by dissociation of hydrogen peroxide. This fact had important implications in the formulation of the experimental design for statistical evaluation of environment variables. It would be very difficult to control oxygen at low concentrations if the hydrogen peroxide was to be at a high concentration. This identified the need to perform a study of the oxygen/hydrogen peroxide/temperature relationship prior to starting the main experimental design. This study confirmed the need to test in oxygen and hydrogen peroxide environments separately.

An experimental design in the "central composite" class was selected. A

symmetric, linear "coded" scale was adopted for each variable; exponential transforms were used for all variables except temperature. The designs and scaling allowed independent estimation of coefficients on terms in (1) an oxygen environment, leading to an oxygen model, and (2) a hydrogen peroxide environment, leading to a hydrogen peroxide model. For each environment, the experimental design included a linear part, for determining the main and interaction effects of the variables, and a quadratic part to investigate curvature in the response surface.

To reflect IGSCC, a CERT parameter combining time to maximum stress and ductility (elongation and reduction of area) was chosen for use in the analyses. Specifically, log adjusted time to maximum stress (LATMS) was the parameter used for the dependent variable. Using LATMS values from each test in the respective environments, multiple regression analysis was used to identify terms with significant coefficients. Prediction equations were obtained for each environment, Equations (5-1) and (5-2) for the oxygen environment and Equations (5-13) and (5-14) for the hydrogen peroxide environment. It was found that sensitized Type 304 stainless steel specimens fabricated from SRP archive piping were susceptible to IGSCC during CERT testing using a crosshead speed of 1.2 mils/hour ($4.4 \times 10^{-7} \text{ sec}^{-1}$) in most simulated SRP coolant environments. Accordingly, the models for each environment were found to be highly significant.

The effect of the environmental variables on IGSCC will now be summarized; important and nonimportant variables will be identified. Subsequently, these effects will be quantified in an "importance analysis".

In both environments, temperature was the most significant variable, IGSCC susceptibility increased with increasing temperature. Referring to Table 5-14, the F-factors for temperature are very high compared to the critical F-factors, regardless of which model is used. As shown in Figure 5-29, a rather steep slope (temperature dependency) is displayed when all of the data are averaged and plotted against failure time for both the oxygen and hydrogen peroxide design tests. There was no IGSCC in any specimens tested at 35 or 40°C, including the specimen tested at the highest concentrations of variables at 35°C in the Option 1 tests. Since IGSCC was predominant in specimens tested in various environments at 55°C, the threshold for cracking in the CERT tests is between 40 and 55°C. Figure 5-29 also shows the average effect of hydrogen peroxide; once present it increases IGSCC. However, the amount of hydrogen peroxide in the range 400 to 5000 ppb was found to be not significant. Furthermore, as shown in Figure 5-24, there was no degrading effect from hydrogen peroxide if the chloride concentration was low (8 ppb); in contrast, it had a large degrading effect when chloride was higher (68 ppb).

In the oxygen environment, sulphate was found to be a significant variable and it also had a significant interaction with temperature. IGSCC decreased with decreasing sulphate concentration, more so at higher temperature (105°C). Chloride, carbon dioxide and oxygen did not significantly affect IGSCC over their respective ranges tested, there was a significant temperature by carbon dioxide interaction however. This was only just significant at the 10% level as seen by its F-factor of 4.0 (Table 5-14, column 5-14B) being marginally over the critical F-factor for

significance of 2.93. The non significance of oxygen was somewhat surprising, since dissolved oxygen is a main contributor to IGSCC of stainless steel in high purity water environments (BWR coolant) at high temperature ($>120^{\circ}\text{C}$). In the SRP environments, it did not matter whether oxygen was added as a gas, resulted from hydrogen peroxide dissociation, or was a combination of the two. It is possible that the large positive chemical potential of the simulated SRP environments had an overriding effect.

In the hydrogen peroxide environment, chloride was found to be highly significant; decreasing chloride decreased IGSCC susceptibility. The F-factor for chloride was 48 (Table 5-14, column 5-14E), which compares to 90 for temperature, and 2.88 for the critical F-factor. There was also an interaction of chloride with sulphate in the hydrogen peroxide environment, although the 3.1 F-factor compared to the critical 2.88 renders this interaction marginal. The chloride squared term was also significant, this implies that as the chloride level is lowered the degradation effects on IGSCC susceptibility improve more rapidly. This effect was shown by the curvature in the response surfaces in Figures 5-21A and 5-21B. In the hydrogen peroxide environment sulphate was not significant, although, as in the oxygen environment, its interaction with temperature was significant. Again, carbon dioxide was not significant.

In an "importance analysis", the prediction equations were used to determine how much a change in each variable could affect IGSCC. This importance analysis is summarized in Table 6-1. This table shows the

relative importance of each variable. It does this by showing the change in ATMS (Adjusted Time to Maximum Stress), as a factor, caused by a change from coded level 0 (nominal, except for TEMPC = 0, TEMP = 80°C) to -1.6. Because of the two-factor interaction terms, these factors may differ depending on the value of other variables, as shown in the table. The factor column shows that, for the change in value stated, temperature is the most important variable. In the hydrogen peroxide environment, changing temperature from 80°C to 40°C is predicted to increase ATMS by a factor from 4.67 to 8.77 depending on the value of sulphate; the larger factor applies when the sulphate is low. Slightly lower than these are the factors for the corresponding change in chloride, 3.81 and 5.62 depending on the sulphate level, with the larger factor again applying when sulphate is low. Thus, chloride could be said to be the second most important variable in the hydrogen peroxide environment. By its lower factors, sulphate is the third most important. A similar pattern prevails in the oxygen environment. Without exception, reduced IGSCC is accomplished by decreasing the value of the variable. Carbon dioxide was not important in either environment; oxygen was not important in its environment and neither hydrogen peroxide nor dissociated oxygen were important in the hydrogen peroxide environment. However, the presence of hydrogen peroxide is an important variable. ECP was not found to be an important variable in either environment.

The adopted hydrogen peroxide model (Equation (5-13)) was used to predict the results of the Option 1 tests. Reasonable agreement between the predicted and observed results was obtained. Thus, the Option 1 tests

successfully validated the model. Similarly, prediction of the one test in Option 1, performed in an oxygen environment, agreed well with its observed value.

Attempts were made to include ECP-SS in the oxygen and hydrogen peroxide models. However, it was found to be not significant. This is not surprising because neither oxygen nor hydrogen peroxide, once present, were significant and it is these which largely fix the ECP-SS value.

6.2 Fulfillment of Objectives

The objectives of Task A were (1) to produce prediction equations for IGSCC in sensitized Type 304 stainless steel from SRP process water piping, and (2) to identify environmental variables detrimental to IGSCC for the purpose of (a) further evaluation of their effect on crack growth rate in Task B, and (b) of direct use in deciding how the SRP environment might be changed to reduce IGSCC of the process water piping.

Objective (1) was accomplished by Equations (5-1), (5-2), (5-13) and (5-14).

Objective (2) was accomplished by the analyses for the importance of variables in Sections 5.3.2.3 and 5.3.3.3 and summarized above. The results suggest that testing in Task B should be in the hydrogen peroxide environment only, varying temperature, chloride and sulphate in that order of priority. Hydrogen peroxide itself need not be varied.

An improved reactor environment can be achieved by reducing chloride and sulphate; it can also be achieved by reducing temperature and/or eliminating hydrogen peroxide entirely.

6.3 Conclusions

Based on the results of this constant extension rate test program some general and specific conclusions can be made.

First, sensitized Type 304 stainless steel specimens fabricated from SRP archive piping were susceptible to IGSCC when tested at an extension rate of 1.2 mil/hour in most of the simulated SRP reactor coolant environments.

Second, The volume of testing, relevant to test repeatability, was adequate to identify some main and quadratic effects and some two-factor interactions as significant. In all cases, the overall models fitted were highly significant. Conclusions regarding these significant effects are listed below.

1. Temperature was determined to be the most significant variable over the range tested (35 - 120°C). An increase in temperature produced more extensive IGSCC. While no IGSCC occurred in specimens tested at 35 or 40°C, IGSCC did occur at 55°C. It appears that a threshold for IGSCC is present in simulated SRP environments at some temperature between 40 and 55°C for a CERT extension rate of 1.2 mil/hour.

2. Oxygen was found to be not significant over the range tested (100 - 8000 ppb) at any test temperature.
3. The presence of hydrogen peroxide over the range 400 to 5000 ppb was only significant when the chloride concentration was 30 ppb or greater; there was no effect at a concentration of 8 ppb chloride.
4. Chloride (2 - 100 ppb) was significant in the presence of hydrogen peroxide over the temperature range 55 - 105°C; chloride was not significant in the oxygen environment. Decreasing the chloride concentration to as low a level as possible is beneficial (2 ppb is less detrimental than 8 ppb on IGSCC susceptibility).
5. Sulphate (7 - 500 ppb) was significant in the oxygen environment, it was not significant in the hydrogen peroxide environment. However, there was a strong temperature by sulphate interaction in both environments; its effect was more detrimental at higher temperatures.
6. Carbon dioxide (20 - 1000 ppb) was not significant in either oxygen or hydrogen peroxide environments. However, there was a temperature by carbon dioxide interaction in the oxygen environments. This interaction suggested that carbon dioxide was detrimental at 105°C but beneficial at 55°C.

7. Electrochemical potential (ECP) was not a significant variable in the CERT tests in either environment. The fact that the ECP during laboratory tests with hydrogen peroxide compared favorably with the ECP measured in SRP reactors is important, and lends credence to the applicability of results developed during this program.

7 8 9 10 11

1	2	3	4	5	6	When the following variables are at the values shown, all other variables at any value, the factor shown.					a)ATMS/a(Variable in first column) is significantly more negative than 0, at the 5% level, and therefore the variable is important in affecting IGSCC susceptibility, when the following variables are in the ranges shown:			
Changing from			to			reduces IGSCC susceptibility as indicated by changing ATMS by the factor shown.					For entire ranges see Figure			

"Entire" = Entire operating region, -1.6 to 1.6 ATMS = Adjusted Time to Maximum Stress, hrs.

Table 6.1. The quantitative importance of each variable in reducing IGSCC susceptibility as a factor in increasing ATMS at selected points; and region of importance of each variable

7.0 REFERENCES

1. Clarke, W.L., et.al., "Comparative Methods for Measuring Degree of Sensitization in Stainless Steel", ASTM STP 656, pp's 99-123, 1978.
2. Clarke, W.L., et.al., "Dynamic Straining Stress Corrosion Test for Predicting Boiling Water Reactor Materials Performance," ASTM STP 665, pp's 149-169, 1979.
3. Clarke, W.L., "The EPR Method for the Detection of Sensitization in Stainless Steel," NUREG/CR-1095 (GEAP-24888) April 1981, available from GPO Sales Program, Div. of Tech. Info. and Doc. Control, USNRC, Wash. DC, 20555
4. Clarke, W.L. and Jacobs, A.J., "Effect of Radiation Environment on SCC of Austenitic Materials," Proceed. Int. Sym. on Environmental Degradation of Materials in Nuclear Power Systems - Water Reactors, NACE, Myrtle Beach, SC, Aug. 1983.
5. Indig, M.E., et.al., "Evaluation of In-Reactor Intergranular Stress Corrosion Cracking via Electrochemical Measurements," Proceed. 2nd Int. Sym. on Environmental Degradation of Materials in Nuclear Power Systems - Water Reactors, NACE, Monterey, Ca., Sept. 1985.

APPENDIX A

Examples of all data collected for Specimen 2A41 during CERT test for period 4/25 - 4/28/87.

Note: The blips shown in the Trend Graphs represent periods when no data was acquired, i.e. system calibration, computer disc full, power interruption, etc.

SRP 2A41

4/25-4/28/87

OXYGEN LOOP C

4/25-4/28/87

ECP DURING CERT 2A41

4/25 TO 4/26/67

On-Line 100 Chloride/ephy Data Report

Test Water - Loop C

DATE	TIME	PH	chloride	Nitrate	Sulfate	DO	peroxide
87	4 24	0.47	27.14	475.64	45.45	270.73	1634.66
87	4 24	0.52	27.24	481.46	46.77	269.75	1663.11
87	4 24	5.58	27.61	481.07	46.63	269.41	1665.95
87	4 24	6.37	28.40	488.14	45.66	273.56	1751.59
87	4 24	11.34	0.00	0.00	0.00	312.05	1938.11
87	4 24	12.58	28.95	494.75	57.44	329.22	2074.66
87	4 24	15.51	28.55	481.00	54.53	340.60	2094.33
87	4 24	17.26	0.00	576.24	0.00	360.49	2245.29
87	4 24	20.01	27.95	478.08	53.68	346.67	2179.08
87	4 24	22.37	27.29	462.02	51.65	354.04	2141.09
87	4 25	1.12	27.63	466.14	51.67	379.86	2081.73
87	4 25	3.48	28.20	500.83	53.18	385.11	2023.43
87	4 25	6.23	19.54	490.72	41.56	350.40	2021.30
87	4 25	9.56	27.76	499.41	54.00	362.62	2100.96
87	4 25	11.34	29.18	479.41	55.54	401.72	2256.46
87	4 25	14.09	29.20	455.81	54.85	384.37	2312.55
87	4 25	16.44	29.64	452.55	54.77	386.09	2263.98
87	4 25	19.20	29.67	478.39	51.96	373.78	2075.09
87	4 25	21.55	29.17	487.80	53.42	371.53	1953.68
87	4 26	0.30	28.78	482.31	52.72	375.66	1974.67
87	4 26	3.06	28.38	472.13	51.56	364.47	1966.97
87	4 26	5.41	28.83	482.94	52.66	380.24	2128.00
87	4 26	8.16	29.03	479.92	52.43	392.95	2076.86
87	4 26	10.51	28.30	469.41	53.39	369.05	2265.01
87	4 26	13.27	28.90	449.15	54.55	392.08	2300.12
87	4 26	16.02	28.75	438.47	52.91	352.33	2236.25
87	4 26	18.37	27.98	456.58	51.01	330.15	2098.76
87	4 26	21.13	1.74	414.08	0.00	351.04	2104.38
87	4 26	23.48	1.67	416.93	0.42	325.18	2191.69
87	4 27	2.23	28.18	479.27	51.27	330.53	2220.45
87	4 27	4.59	28.30	487.32	52.89	327.00	2174.76
87	4 27	7.34	4.65	437.95	0.00	320.01	2160.57
87	4 27	10.48	29.35	514.15	54.99	318.49	2103.96
87	4 27	12.44	29.64	507.04	55.39	321.15	2286.98
87	4 27	14.49	29.46	481.79	55.50	318.66	2086.99
87	4 27	16.30	29.15	473.85	53.58	324.51	2291.88
87	4 27	19.06	30.00	483.98	54.25	335.31	2049.76
87	4 27	21.41	30.92	513.90	53.50	342.15	2073.05
87	4 28	0.16	30.46	510.09	54.97	323.74	2229.27
87	4 28	2.51	30.09	512.76	56.27	326.32	2297.24
87	4 28	5.27	0.00	439.67	0.00	335.21	2224.73
87	4 28	8.02	31.02	520.92	53.22	314.20	2131.00
87	4 28	9.37	32.27	541.47	0.00	323.18	2029.50
87	4 28	11.43	32.72	539.93	57.55	320.28	2168.82
87	4 28	13.49	32.51	533.42	56.64	344.46	2270.49
87	4 28	15.54	32.39	523.27	56.57	328.00	2276.53
87	4 28	17.30	32.58	519.16	55.84	343.34	2546.54
87	4 28	20.05	32.64	512.06	54.22	362.90	2358.83
87	4 28	22.41	32.86	519.08	53.74	336.83	2434.18
87	4 29	1.16	32.33	517.51	53.36	334.56	2282.44
87	4 29	3.51	33.19	525.19	52.63	338.30	2283.27
87	4 29	6.26	7.94	462.58	0.00	317.57	2093.35

SAVANNAH RIVER 1 - TREND GRAPH

SAVANNAH RIVER 1 - TREND GRAPH

SAVANNAH RIVER 1 - TREND GRAPH

SAVANNAH RIVER 1 - TREND GRAPH

SAVANNAH RIVER 1 - TREND GRAPH

APPENDIX B

**Main Variable Chemical Analyses
Plotted Within the Established
Tolerance Limits**

TEST WATER - MOM LOOP (wks MOMLP61)

CERT TEST #2A61-MOM file NITR61

TEST WATER - MOM LOOP (wks MOMLP61)

CERT TEST #2A61-MOM file PEROX61

TEST WATER - MOM LOOP (wks MOMLP61)

CERT TEST #2A61-MOM file CHLOR61

TEST WATER - MOM LOOP (wks MOMLP61)

CERT TEST #2A61-MOM file SULP61

TEST WATER - MOM LOOP (wks MOMLP61)

CERT TEST #2A61 - MOM #10 DIOX61

END

**DATE
FILMED**

3 / 1 / 93