G-41-629

DOE/ER/45266--T3

STUDY OF HIGH T_c SUPERCONDUCTING THIN FILMS

GROWN BY MOCVD

DOE/ER/45266--T3

DE93 005052

Final Report

July 1, 1986 - April 30, 1990

Principal Investigator:

Ahmet Erbil

School of Physics

Georgia Institute of Technology

Atlanta, Georgia 30332

Tel.: (404) 894-6817

PREPARED FOR THE U. S. DEPARTMENT OF ENERGY

GRANT NO. DE-FG05-86ER45266

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

da
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	page
1. Introduction.	1
2. Study of Artificially Layered Materials	1
2.1 Thin Film Growth	1
2.2 CVD Precursor Development.	2
2.3 Study of Non-oxide Thin Films by MOCVD	2
3. Study of Naturally Layered Oxide Superconductors.	5
3.1 Oxide Bulk Material Studies.	5
3.2 Oxide Thin Film Studies.	6
4. Publications Under This Grant	8
5. Meetings and Symposia Under the Grant	9
6. Patent Disclosure Under This Grant.	10

STUDY OF HIGH T_c SUPERCONDUCTING THIN FILMS

GROWN BY MOCVD

1. Introduction:

In this report, we provide a summary of the progress made during the grant period (July 1, 1986 - April 30, 1990). Initially the focus of this program was on the development of underlying science and technology for the fabrication of metal-semiconductor superlattices. The major motivation for this work was to search for excitonic superconductivity in these structures as predicted by theory, in addition to the obvious microelectronic applications. After the discovery of superconductivity with transition temperatures above 77K, naturally we have turned our attention also to this new class of materials.

We describe briefly below our work carried under this program on the development of techniques to grow metal-semiconductor superlattices (artificially layered materials) and on the copper oxide based superconductors (naturally layered materials).

2. Study of Artificially Layered Materials

2.1 Thin Film Growth

Currently the major growth technique utilized is the metalorganic chemical vapor deposition (MOCVD) technique. This technique has the capability to grow thin films with atomic level control to fabricate heterostructures and superlattices. The MOCVD technique is also very suitable to the large scale production of electronic and photonic thin films. We have three MOCVD systems operational. The first one is a commercial MOCVD system (Cambridge Instruments, MR102) with 5 MO source lines and 2 hydride lines, suitable for the deposition of a single layer, heterostructure and superlattices. The other two MOCVD systems are homemade and suitable for the

deposition of oxide thin films.

2.2 CVD Precursor Development

The availability of the suitable precursors are essential for successful deposition of the films by the CVD technique. This component of the program focuses on the creation of novel metalorganic compounds suitable for the deposition of rare earth metals, particularly for the deposition of La and LaTe by MOCVD. We have had major breakthroughs in this area in the past three years. I believe that this puts us in a unique position in the world in the deposition of all of the rare earth metals. These precursors will have applications in the metallization of microcircuitry, in the deposition of protective coatings, newly discovered Cu based oxide superconductors and solar cells, etc. A patent has been awarded to cover these inventions.

2.3 Study of Non-Oxide Thin Films Grown by MOCVD

In this area, our purpose was to understand the growth conditions and their relationship to the properties of the thin films obtained. Even though the immediate goal was to establish a data base for the growth of LaTe/PbTe superlattices on CdTe buffer layers grown on GaAs, the work has much broader applications in microelectronics and optoelectronics. Among the major achievements in this area are: detailed understanding of the growth mechanism of MOCVD, successful deposition of high quality PbTe films by MOCVD, and first successful deposition of La and LaTe films by MOCVD. The films grown have been characterized for their chemical, structural, electrical and optical properties. The results will be submitted soon for publication in the form of several papers, despite delay due to higher priority given to oxide thin films.

In the study of the MOCVD growth mechanism, we have grown CdTe films on GaAs (111) wafers systematically to relate the growth rate and the surface

morphology to the growth conditions. It is important to understand the growth of CdTe layers, because such layers will be used as the buffer layers for the growth of LaTe/PbTe superlattices. By using a mass transport model through the boundary layer and the gas-solid interface, we have calculated the growth rate as a function of temperature for a broad range, including the mass input limited regime, the diffusion limited regime and the surface kinetic limited regime. We have obtained excellent agreement between the theory and the experiments, as discussed in the preprint attached. On the theoretical side, we have interacted very closely with Prof. Zangwill in the School of Physics at Georgia Tech. Currently, we are extending our understanding of MOCVD from CdTe to growth of other compounds such as PbTe, LaTe and LaTe/PbTe. This work has been carried out in collaboration with P. Anderson of Texas Instruments.

The [111] CdTe/[111] GaAs heterostructure system has been studied in detail by means of MeV ion channeling. It is found that the epitaxy is quite good (backscatter minimum yields of 15%) for thickness greater than 100 Å, which is remarkable considering the 14% lattice mismatch between film and substrate. We have shown that the mismatch results in defects in the interface region in addition to strain produced by epitaxial growth. It has been observed that there is a disturbance in the Cd sublattices as evidenced by displaced Cd atoms protruding into the [211] channels in an asymmetric manner causing an apparent offset in the Cd angular yield minimum. A model was proposed based on Te vacancy density of 1.7% as a possible explanation for the Cd behavior. This work has been in collaboration with B. Wilkens at Bellcore.

We have grown epitaxial layers of PbTe on either GaAs wafers or on CdTe buffer layers grown on GaAs wafers. PbTe grows epitaxially with the [111] direction on GaAs(100) and [100] direction on GaAs(111). Tetraethyllead and diisopropyltelluride were used as the MOCVD precursors for low temperature deposition (temperature range 320-450 C). The PbTe films were n- or p-type

depending on the growth conditions. The IR transmission measurements have indicated a sharp absorption at the band-gap energy. We used both Hall effect and IR reflectivity measurements to determine the carrier concentration and mobilities. The mobility for MOCVD grown PbTe films was smaller than the bulk value. This may be a result of microcracks in the film due to thermal expansion mismatch. In support of this idea is the observation of microcracks in most of the PbTe films grown under the optical microscope.

We have deposited La and LaTe thin films in the homemade MOCVD system by using the precursors discovered at Georgia Tech. The suitable deposition temperature range was 550-650 C. These studies were preliminary in nature and were aimed at understanding the decomposition kinetics of the new precursors. Quartz plates were used as substrates. We utilized both argon and hydrogen as the carrier gas. Electron microprobe analysis exhibited up to 10% carbon incorporation in La films grown with Ar carrier gas. We expect great reduction in carbon incorporation in films grown with hydrogen carrier gas. We are in the process of analyzing these films. Also we have observed much less carbon incorporation in LaTe films.

Epitaxial thin films of bismuth telluride, Bi_2Te_3 , have been successfully deposited first time on GaAs(111) by MOCVD. Bi_2Te_3 thin films were metallic and can be used to deposit metal-semiconductor superlattices. Also, Bi_2Te_3 is a thermoelectric material and may be used to fabricate monolithic micro-refrigerators to cool semiconductor or superconductor devices. High quality epitaxial films of Bi_2Te_3 were obtained on GaAs(111) substrates at 320°C as evidenced by optical microscopy, x-ray diffraction and ion channeling. Film properties, such as mobility and carrier concentration were studied in the temperature range 80-300K. The films were of p-type with a carrier concentration of $2 \times 10^{20} \text{ cm}^{-3}$ at room temperature.

We have utilized various on or off-campus facilities to carry out the characterization of thin films. Double crystal x-ray diffraction experiments

were carried out in collaboration with P. Huang and S. Stock of Materials Engineering, the electron microprobe analysis by G. Freeman of Georgia Tech Research Institute, and IR reflectivity measurements by S. Perkowitz of Emory University. We have also utilized the Hall effect system in A. Rohatgi's laboratory in Electrical Engineering.

We feel that we have acquired large enough data base for the growth of metal-semiconductor superlattices to search for excitonic superconductivity. However, we would like to continue this line of research at a slower pace and concentrate on the artificially layered oxide compounds in the near future, because we can make an immediate impact in this area.

3. Study of Naturally Layered Oxide Superconductors

3.1 Oxide Bulk Material Studies:

Right after the announcement of the breakthrough on the copper-oxide-based high T_c superconductors, we initiated a program on these materials. Even though this effort was initially started by using the funds from a Sloan Research Fellowship and an IBM Faculty Development award, there have been clear overlaps with our DOE contract starting in the summer of 1987.

Our initial work in this area involved the synthesis and characterization of $Y_{1-x}Ba_xCu_3O_{7-\delta}$ compounds in the usual manner. By optimizing the heat treatment and making substitution, we were able to obtain superconductors on a routine basis with transition temperatures above 90 K. Starting in July of 1987, our focus shifted to the discovery of superconductivity at even higher temperatures. After a careful systematic study, we were led to several compositions exhibiting evidence of possible superconductivity at room temperature or above. The highest observed onset temperature is 550 K. This work is described in detail in a paper submitted to Physical Review B. The fraction of the superconducting phase seems to be very small (1 part in 10^4).

3.2 Oxide Thin Film Studies:

Our research effort in this area in the past two years has focused on the development of the MOCVD technique to provide high quality superconducting thin films on large area substrates for fundamental studies and device applications. We have successfully deposited thin films of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ and $\text{Th}_2\text{CaBa}_2\text{Cu}_2\text{O}_y$ by MOCVD with high quality. The results have been reported in the form of several papers and invited talks. The papers are provided in the attachment. Our results show that after post annealing, C-axis oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ superconducting films can be obtained reproducibly with a transition onset temperature at 93K and a zero-resistance temperature at 84K on yttria-stabilized zirconia (100) (YSZ) substrates. Superconducting $\text{Th}_2\text{CaBa}_2\text{Cu}_2\text{O}_y$ thin films have been grown on single crystal sapphire (1102) substrate without a buffer layer. Superconducting transition temperatures with onset above 100K and zero-resistance at 94K has been obtained with heat treatment at 500°C in oxygen.

The use of superconducting coatings and thin films is severely limited at this point because of the lack of suitable substrates. The most widely used substrates are MgO(100), YSZ and SrTiO_3 . However, these substrates are very expensive and not available with large areas. To address this problem we have started depositing these materials by MOCVD on common substrates, such as glass plates, silicon and sapphire. The MgO film deposited on a glass plate had very smooth surface morphology and was optical quality. It had also almost one hundred percent texturing with (100) direction perpendicular to the substrate surface. The detailed results are provided in a paper provided in the attachment. This is surprising in view of the fact that glass substrate is amorphous and MgO has a cubic structure. Next we would like to deposit superconducting thin films on these (100) oriented MgO buffer layers deposited on glass plates. It is well known that single crystal MgO (100) substrates

give high quality superconducting films with very high critical currents ($T_c \sim 10^6 \text{ A/cm}^2$). Therefore the growth of oriented MgO films on common cheap substrates as buffer layers may have profound implications for the large scale utilization of the superconducting thin films and coatings.

4. Publications Under This Grant

1. "Evidence for Possible Stable Superconductivity at 500K", A. Erbil, A. C. Wright and E. P. Boyd, Phys. Rev. B 37, 555 (1988).
2. "Metalorganic Chemical Vapor Deposition of Highly Textured Superconducting $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Films", K. Zhang, B. S. Kwak, E. P. Boyd, A. C. Wright and A. Erbil, in "Science and Technology of Thin Film Superconductors", ed. by R. D. McConnell and S. A. Wolf (Plenum, New York, 1989), p. 271.
3. "C-Axis Oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Superconducting Films by Metalorganic Chemical Vapor Deposition", K. Zhang, B. S. Kwak, E. P. Boyd, A. C. Wright and A. Erbil, Appl. Phys. Lett. 54, 380 (1989).
4. "Metalorganic Chemical Vapor Deposition of [100] Textured MgO Thin Films", B. S. Kwak, E. P. Boyd, K. Zhang, A. Erbil, and B. Wilkens, Appl. Phys. Lett. 54, 2542 (1989).
5. "Metalorganic Chemical Vapor Deposition of $\text{Tl}_2\text{CaBa}_2\text{Cu}_2\text{O}_y$ Superconducting Thin Films on Sapphire", K. Zhang, E. P. Boyd, B. S. Kwak, A. C. Wright, and A. Erbil, Appl. Phys. Lett. 55, 1258 (1989).
6. "MeV Ion Channeling Studies of [111] CdTe Films on [111] GaAs Substrates", B. Wilkens, K. Pollard and A. Erbil, J. Appl. Phys. 66, 5096 (1989).

Accepted for Publication

1. "Metalorganic Chemical Vapor Deposition of Ferroelectric BaTiO_3 Thin Films", B. S. Kwak, K. Zhang, A. Erbil and B. J. Wilkens, to be published in January 1991 in J. Appl. Phys.

In Preparation

1. "Growth Mechanism of CdTe Films by Organometallic Vapor Phase Epitaxy", A. Erbil and P. L. Anderson (for Appl. Phys. Lett.).
2. "OMVPE Growth and Properties of PbTe Films on GaAs", A. Erbil and K. T. Pollard (for Appl. Phys. Lett.).
3. "Organometallic Vapor Phase Epitaxy of Bi_2Te_3 on GaAs (111)", A. Erbil, K. T. Pollard and B. Wilkens (for J. Electronic Mat.).

5. Meetings and Symposia Under This Grant

A) Invited

1. A. Erbil, "Possible Very High T_c Superconductors", Panel discussion, Materials Research Society Meeting, April 5-8, 1988, Reno, Nevada.
2. A. Erbil, K. Zhang, B. S. Kwak, E. P. Boyd and A. C. Wright, "C-Axis Oriented $YBa_2Cu_3O_{7-x}$ Superconducting Films by Metalorganic Chemical Vapor Deposition", Conference on the Science and Technology of Thin Film Superconductors, November 14-18, 1988, Colorado Springs, Colorado.
3. A. Erbil, K. Zhang, B. S. Kwak and E. P. Boyd, "A Review of Metalorganic Chemical Vapor Deposition of High-Temperature Superconducting Thin Films", SPIE's 1989 Symposium, Oct. 8-13, 1989, Santa Clara, CA.

B) Contributed

1. A. Erbil and P. L. Anderson, "MOCVD Growth Mechanisms of II-VI Compounds", Bull. Am. Phys. Soc. 32, 530 (1987).
2. P. L. Anderson and A. Erbil, "MOCVD of II-VI Compounds", Epicon '87, November 16-20, 1987, South Africa.
3. A. Erbil, A. C. Wright and E. P. Boyd, "Evidence for Possible Stable Superconductivity at 500 K", Symp. High T_c Superconductors, Materials Research Society, Nov. 30-Dec. 3 (1987), Boston, MA.
4. A. Erbil and K. T. Pollard, "Study of MOCVD Grown PbTe Films", Bull. Am. Phys. Soc. 33, 246 (1988).
5. B. Wilkens and A. Erbil, "Ion Channeling Studies of the MOCVD Grown CdTe Films on GaAs", Materials Research Society Meeting, Boston, MA, Nov. 28 - Dec. 3, 1988.
6. A. Erbil, K. Zhang, B. S. Kwak, E. P. Boyd and A. C. Wright, "C-Axis Oriented $YBa_2Cu_3O_{7-x}$ Superconducting Films by Metalorganic Chemical Vapor Deposition", Conference on the Science and Technology of Thin Film Superconductors, November 14-18, 1988, Colorado Springs, Colorado.
7. K. Zhang, B. S. Kwak, E. P. Boyd, A. C. Wright, and A. Erbil, "Effects of Substrate and Post-Annealing Conditions on Metalorganic Chemical Vapor Deposition of $YBa_2Cu_3O_{7-x}$ Thin Films", Bull. Am. Phys. Soc. 34, 603 (1989).
8. A. Erbil, K. Pollard and B. Wilkens, "Study of Bi_2Te_3 Thin Films Grown by MOCVD", Bull. Am. Phys. Soc. 34, 937 (1989).
9. B. S. Kwak, E. P. Boyd, K. Zhang, and A. Erbil, "Growth of Highly Textured MgO Thin Films by MOCVD", Bull. Am. Phys. Soc. 34, 937 (1989).

6. Patent Disclosure Under This Grant

1. A. Erbil, "Volatile Compounds of Group IIIB Elements for CVD", 1989.
U. S. Patent 4,882,206.
2. B. S. Kwak, A. Erbil, "[100] Oriented MgO Films by MOCVD", 1988.
3. K. Zhang, A. Erbil, "C-Axis Oriented $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Superconducting Films
by Metalorganic Chemical Vapor Deposition", 1988.

*reprints and preprints
removed; conf paper
cycled separately.
ds*

**DATE
FILMED
01/22/93**