Received by OSTI DOE/CE/23810-4C

JAN 29 1993

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ELASTOMERS

DOE/CE/23810--4C

Quarterly Report

DE93 006429

1 July 1992-30 September 1992

Dr. Gary R. Hamed
Robert H. Seiple

Institute/Department of Polymer Science
Polymer Science Building
University of Akron
Akron, Ohio 44325-3909

October 1992

Prepared for
The Air-Conditioning and Refrigeration Technology Institute
Under
ARTI MCLR Project Number 650-50500

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.94 % of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.06 % of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

for

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

(for journal publication submissions)

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institute, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyrights covering this paper.

COMPLIANCE WITH AGREEMENT

The University of Akron has complied with all aspects of the agreement.

PRINCIPAL INVESTIGATOR EFFORT

Dr. Gary Hamed and R.H. Seiple are the principal investigators for the UA/ARTI MCLR program. During the second quarter of the contract period, Dr. Gary Hamed has devoted a total of 25 hours (5 % of his available work hours) and R. Seiple has devoted 200 hours (40 % of his available work hours) on the UA/ARTI MCLR program.

1

TABLE OF CONTENTS

ABSTRACT	2
SCOPE	2
SIGNIFICANT RESULTS	3
DISCUSSION	3-5
Figure 1a Elastomer Diameter Change in R-123	6-7
Figure 1b Elastomer Diameter Change in R-142b	8-9
Figure 1c Elastomer Diameter Change in R-124	10-11
Figure 1d Elastomer Diameter Change in R-22	12-13
Figure 2a Elastomer Diameter Change in R-125	14-15
Figure 2b Elastomer Diameter Change in R-134a	16-17
Figure 2c Elastomer Diameter Change in R-143a	18-19
Figure 2d Elastomer Diameter Change in R-152a	20-21
Figure 2e Elastomer Diameter Change in R-32	22
Figure 3a Elastomer Diameter Change in Alkyl Benzene	23-24
Figure 3b Elastomer Diameter Change in Mineral Oil	25-26
Figure 3c Elastomer Diameter Change in Pentaerythritol Ester Mixed Acid	27-28
Figure 3d Elastomer Diameter Change in Pentaerythritol Ester Brached Acid	29-30
Figure 3e Elastomer Diameter Change in Polypropylene Glycol Diol	31-32
Figure 3f Elastomer Diameter Change in Polypropylene Glycol Butyl Monoether	33-34
Figure 3g Elastomer Diameter Change in Modified Polyglycol	35-37
APPENDIX A ELASTOMER SWELL DATA	38-133
APPENDIX B TEST METHODOLOGY	134-137
APPENDIX C VENDOR SUPPLIED GASKET MATERIAL FORMULATION NUMBERS AND ID	138-139

COMPATIBILITY OF REFRIGERANTS AND LUBRICANTS WITH ELASTOMERS

ABSTRACT

The information contained in this report is designed to assist the air-conditioning and refrigeration industry in the selection of suitable elastomeric gasket and seal materials that will prove useful in various refrigerant and refrigeration lubricant environments. 97 % of the swell measurements have been made to date. The other 3 % of the measurements are contingent on the availability of additional quantities of R-32. Swell behavior in the fluids have been determined using weight and in situ diameter measurements for the refrigerants and weight, diameter and thickness measurements for the lubricants. Weight and diameter measurements are repeated after 2 hours and 24 hours for samples removed from the refrigerant test fluids and 24 hours after removal from the lubricants.

SCOPE

The Compatibility of Refrigerants and Lubricants with elastomers program is an 11 month research effort supported by a grant from the Department of Energy through the Air-Conditioning and Refrigeration Technology Institute. The elastomers research effort was initiated at the University of Akron on March 1, 1992 and is expected to continue through January 31, 1991.

First quarter (Jan 1, 1992-Mar 31, 1992) efforts centered around ordering materials, mixing some of the 84 compounds needed for the study and the fabrication of 120 pressure vessels required for the in situ evaluation of the swell behavior of elastomers in refrigerants. The moisture content was determined for the lubricant samples.

Second quarter (April 1, 1992-Jun 30, 1992) efforts revolved around the implementation of proposed methodologies for the acquisition of elastomer swell data in refrigerants and lubricants. During the second quarter, swell tests were begun and the appropriate measurements were made on approximately 50 % of the proposed elastomer formulations.

Third quarter (July 1, 1992-September 30, 1992) efforts centered around the completion of phase I work. Approximately 97 % of the Phase I testing has been completed. Work also focused on preparing immersion pressure vessels for the Phase II work effort.

Significant Results

Presently, nearly all of the rubber formulations (#1-85) proposed have been tested for swell in refrigerants: R-123, R-142b, R-124, R-22, R-125, R-134, R-134a, R-143a, R-152a, R-32, and in lubricants: alkyl benzene (AB), mineral oil (MO), pentaerythritol ester mixed acid (PEMA), pentaerythritol ester branched acid (PEBA), polypropylene glycol diol (PPGD), polypropylene glycol butyl monoether (PPGBM), or a modified polyglycol (MPG). The rubber formulations include general purpose and specialty thermoset elastomers, and thermoplastic elastomers. Some compounds were filled, others were not. In addition, several vendor supplied materials (#86-95) have been tested for swelling resistance in the various fluids. Results are given in Figures 1-3: Figures 1a-1d for the HCFCs, Figures 2a-2f for the HFCs, and Figures 3a-3g for the lubricants. Solid bars (with brief composition descriptors) are used to show the in situ percent change in diameter after 14 days of immersion. A blank indicates that the composition has not been tested. In all cases, filled compositions had less swelling compared to corresponding unfilled ones. R-123, the dichloro-substituted HCFC, generally gave the greatest swelling. There were, however, several compositions which swelled little in this refrigerant, including EPDM/PP thermoplastic elastomers (#45-48), a butyl rubber/PP TPE (#85), and four of the vendor supplied compositions (#88-91, 93). Some compositions (e.g., #46-48) shrunk during immersion, indicating that the swellant was removing plasticizer from the rubber.

The refrigerants with the next highest swelling power were the monochlorinated HCFCs, R-124 and R-22, which usually had similar swelling behavior. A notable exception was #91, which swelled significantly in R-22 but not in R-124. Compositions #45-48, #56-57, #74, #86, #88-90, #92-93 all had good resistance to R-124 and R-22. The other monochlorinated HCFC, R-142b, swelled most elastomers less than the previous two. Epichlorohydrin and nitrile elastomers were much more resistant to R-142b than they were to R-124 or R-22. Additionally, compositions #45-48, #49-51, #56-59, #63, #85-93, and #95 were resistant to R-142b.

The HFCs (Figures 2a-2f) give much less swelling than the HCFCs. The two tetrafluoroethane isomers, R-134 and R-134a, show similar swelling behavior. The fluoroelastomers and fluorosilicone elastomers exhibit high swelling in the HFCs. However, most of the elastomer samples have 5% or less increase in diameter after immersion in the HFCs. A great variety of elastomers are resistant to swelling in the HFCs including both the inexpensive, general purpose hydrocarbon elastomers as well as several of the specialty and thermoplastic elastomers. Among the vendor samples submitted #94 is clearly the worst for swelling resistance. Some of the vendor samples resisted swelling in all refrigerants.

The hydrocarbon lubricants, AB and MO, greatly swelled the general purpose hydrocarbon elastomers, while the nitrile rubbers, fluoroelastomers, and nitrile/PP thermoplastic elastomers were quite resistant to these lubricants. The glycol and ester lubricants

swelled the hydrocarbon elastomers a little. The two pentaerythritol ester lubricants (PEMA and PE BA) gave similar swelling behavior.

Several of the compositions including some of the vendor supplied materials were resistant to swelling in all lubricants. These included: #89-93, #17-18, #28-30, #53-55, #49-51, and #56-59.

In Situ Diameter Change
14 Days In R-123
(1,1-Dichloro-2,2,2-Trifluoroethane)

FIGURE 1a

In Situ Diameter Change
14 Days In R 123
(1,1-Dichloro-2,2,2-Trifluoroethane)

FIGURE 1b

In Situ Diameter Change
14 Days In R-142b
(1-Chloro-1,1-Difluoroethane)

FIGURE 1b

In Situ Diameter Change
14 Days In R-142b
(1-Chloro-1,1-Difluoroethane)

In Situ Diameter Change 14 Days In R-124 (1-Chloro-1,2,2,2-Tetrafluoroethane)

FIGURE 1c

In Situ Diameter Change 14 Days In R-124

(1-Chloro-1,2,2,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-22
(Chlorodifluoromethane))

FIGURE 1d

In Situ Diameter Change
14 Days In R-22
(Chlorodifluoromethane)

In Situ Diameter Change
14 Days In R-125
(Pentafluoroethane)

In Situ Diameter Change
14 Days In R-125
(Pentafluoroethane)

In Situ Diameter Change
14 Days In R-134
(1,1,2,2-Tetrafluoroethane)

FIGURE 2b

In Situ Diameter Change
14 Days In R-134
(1,1,2,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-134a
(1,1,1,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-134a
(1,1,1,2-Tetrafluoroethane)

In Situ Diameter Change
14 Days In R-143a
(1,1,1 Trifluoroethane)

In Situ Diameter Change
14 Days In R-143a
(1,1,1-Trifluoroethane)

In Situ Diameter Change
14 Days In R 152a
(1,1 Difluoroethane)

In Situ Diameter Change
14 Days In R-152a
(1,1-Difluoroethane)

In Situ Diameter Change 14 Days In R-32 (Difluoromethane)

Diameter Change 14 Days In Lubricant (Alkyl Benzene)

Diameter Change 14 Days In Lubricant (Alkyl Benzene)

Diameter Change 14 Days In Lubricant (Mineral Oil)

Diameter Change 14 Days In Lubricant (Mineral Oil)

Diameter Change 14 Days In Lubricant (pentaerythritol ester mixed acid)

Diameter Change
14 Days In Lubricant
(pentaerythritol ester mixed acid)

Diameter Change
14 Days Lubricant
(pentaerythritol ester branched acid)

Diameter Change
14 Days In Lubricant
(pentaerythritol ester branched acid)

Diameter Change 14 Days In Lubricant (polypropylene glycol diol)

Diameter Change 14 Days In Lubricant (polypropylene glycol diol)

Diameter Change 14 Days In Lubricant (polypropylene glycol butyl monoether)

Diameter Change
14 Days In Lubricant
(polypropylene glycol butyl monoether)

Diameter Change 14 Days In Lubricant (modified polyglycol)

Diameter Change 14 Days In Lubricant (modified polyglycol)

APPENDIX A

Formula # 1

Ingredient	pphr
Polyisoprene	100
Zinc Oxide	5
Stearic Acid	2
Sulfur	2.25
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	10.3	10.4	10.2	[45.3/42.4] 43.9
R-32	2.8	2.7	2.7	[8.9/8.6] 8.8
R-124	5.6	5.6	5.8	[30.2/29.8] 30.0
R-134a	1.4		1.2	[4.9/4.8] 4.9
R-125	4.6	4.2	4.2	[14.9/14.3] 14.6
R-143a	2.2	1.7	1.9	[5.4/4.9] 5.2
R-152a	4.1	4.2	4.2	[12.3/13.1] 12.7
R-123	48.1	47.5	48.0	[328/327] 328.0
R-142b	10.3	10.0	10.2	[40.1/38.7] 39.4
R-134	1.7	1.5	1.5	[7.8/7.6] 7.7
AB	41.8	-	[57.3/55.7] 56.5	[264/261] 263.0
MO	43.1	-	[53.1/53.2] 53.2	[248/247] 247.0
PEMA	16.1	-	[29.2/28.0] 28.6	[117/113] 115.0
PEBA	Mw.6	-	[26.5/25.7] 26.1	[106/104] 105.0
PPGD	1.0	-	[2.1/2.2] 2.2	[7.9/7.7] 7.8
PPGBM	4.3	-	[8.1/8.0] 8.1	[28.1/27.8] 28.0
MPG	1.7	-	[2.3/2.8] 2.6	[8.5/8.6] 8.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 2

Ingredient	pphr
Polyisoprene	100
Zinc Oxide	5
Stearic Acid	2
Sulfur	2.25
N-(t-butyl)-2-benzothiazyl sulfenamide	0.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	mean	% Wgt. Chg. mean
R-22	9.3	9.3	9.0	[33.3/30.8]	32.1
R-32	1.7	1.6	1.4	[4.9/4.8]	4.9
R-124	5.5	5.8	5.6	[22.4/22.5]	22.5
R-134a	1.1		1.0	[3.7/3.8]	3.8
R-125	2.9	2.8	3.1	[9.5/8.7]	9.1
R-143a	2.0	2.5	2.2	[3.8/3.4]	3.6
R-152a	2.2	2.3	2.5	[8.1/8.3]	8.2
R-123	36.0	36.0	37.6	[220/221]	221.0
R-142b	7.8	7.8	7.8	[31.2/29.8]	30.5
R-134	1.3	1.3	1.1	[5.7/5.7]	5.7
AB	29.5	-	[46.2/45.9] 46.1	[186/182]	184.0
MO	31.0	-	[41.1/40.3] 40.7	[166/165]	165.0
PEMA	11.5	-	[21.8/21.6] 21.7	[77.6/77.6]	77.6
PEBA	9.8	-	[18.4/17.9] 18.2	[65.9/62.9]	64.4
PPGD	1.6	-	[2.3/2.1] 2.2	[6.6/6.5]	6.6
PPGBM	3.4	-	[7.0/6.2] 6.6	[21.0/20.6]	20.8
MPG	1.0	-	[2.2/2.1] 2.2	[7.0/7.0]	7.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 3

Ingredient	pphr
Polyisoprene	100
Zinc Oxide	5
Stearic Acid	2
N-oxidiethylene-2-benzothiazyl-sulfenamide	1
Tetramethylthiuram disulfide	1
Di-morpholino disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
			mean	mean
R-22	9.6	10.1	8.9	[44.4/42.5] 43.5
R-32	1.3	0.8	1.5	[4.7/4.4] 4.6
R-124	6.5	6.5	6.1	[28.2/28.3] 28.3
R-134a	1.0		1.2	[3.8/3.4] 3.6
R-125	3.3	2.9	2.7	[10.3/10.1] 10.2
R-143a	2.0	2.5	2.7	[4.6/4.1] 4.4
R-152a	3.1	2.8	3.1	[8.3/9.5] 8.9
R-123	52.7	52.3	51.8	[386/390] 388.0
R-142b	9.2	9.1	9.5	[40.1/39.1] 39.6
R-134	0.8	0.9	1.0	[6.3/5.9] 6.1
AB	47.0	-	[56.2/55.6] 55.9	[257/257] 257.0
MO	49.5	-	[56.7/57.0] 56.9	[271/272] 271.0
PEMA	18.8	-	[22.0/21.9] 22.0	[83.1/83.2] 83.2
PEBA	14.7	-	[20.3/20.2] 20.3	[75.8/76.4] 76.1
PPGD	0.6	-	[0.7/0.6] 0.7	[1.4/1.7] 1.6
PPGBM	4.5	-	[5.7/5.9] 5.8	[17.7/18.1] 17.9
MPG	1.2	-	[1.8/2.2] 2.0	[5.7/6.4] 6.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 4

Ingredient

pphr

Poly(chlorobutadiene)	100
Zinc Oxide	5
Stearic Acid	0.5
Magnesium Oxide	4

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day	
				mean	mean
R-22	6.3	6.1	6.1	[22.2/21.6]	21.9
R-32	1.1	1.1	1.0	[4.3/4.4]	4.4
R-124	1.9	2.7	2.8	[10.3/10.1]	10.2
R-134a	1.1		1.2	[3.4/3.4]	3.4
R-125	1.4	2.4	2.7	[5.5/5.0]	5.3
R-143a	1.1	1.3	1.2	[3.3/3.6]	3.5
R-152a	2.9	3.1	3.0	[7.6/7.5]	7.6
R-123	16.0	15.6	15.3	[65.0/65.2]	65.1
R-142b	6.6	6.6	6.5	[18.4/18.6]	18.5
R-134	-0.1	0.3	0.6	[3.3/3.4]	3.4
AB	10.0	-	[19.6/20.1]	19.9	[51.1/53.2] 52.2
MO	12.9	-	[26.5/26.0]	26.3	[74.7/71.9] 73.3
PEMA	25.7	-	[53.7/53.3]	53.5	[202/211] 206.0
PEBA	11.4	-	[35.4/26.0]	30.7	[128/77] 103.0
PPGD	3.7	-	[7.3/7.9]	7.6	[19.9/18.7] 19.3
PPGBM	4.8	-	[12.3/11.4]	11.9	[29.7/31.1] 30.4
MPG	0.4	-	[3.9/4.1]	4.0	[11.7/12.0] 11.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 5

Ingredient	pphr
Poly(chlorobutadiene)	100
Zinc Oxide	5
Stearic Acid	0.5
Magnesium Oxide	4
N330 Carbon Black	30

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	4.8	4.9	4.9		[17.2/16.8]	17.0
R-32	1.3	1.6	1.4		[3.7/3.6]	3.7
R-124	1.1	2.8	1.6		[7.6/7.7]	7.7
R-134a	0.6		1.0		[2.7/2.6]	2.7
R-125	0.5	1.8	2.1		[4.6/4.6]	4.6
R-143a	0.4	0.9	0.8		[2.5/2.1]	2.3
R-152a	2.5	2.9	2.9		[5.6/5.9]	5.8
R-123	11.9	11.8	11.4		[48.9/49.5]	49.2
R-142b	4.6	5.1	4.8		[14.4/14.5]	14.5
R-134	0.4	0.9	0.9		[2.7/2.7]	2.7
AB	7.6	-	[16.1/15.3]	15.7	[23.5/38.5]	31.0
MO	7.9	-	[18.9/18.2]	18.6	[49.0/48.4]	48.7
PEMA	12.5	-	[30.5/28.7]	29.6	[93.0/91.8]	92.4
PEBA	7.3	-	[22.1/22.1]	22.1	[65.9/63.6]	64.9
PPGD	2.5	-	[5.0/4.8]	4.9	[13.2/13.9]	13.6
PPGBM	3.2	-	[9.2/9.5]	9.4	[23.0/23.0]	23.0
MPG	8.4	-	[2.8/2.9]	2.9	[8.3/6.7]	7.5

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 6

Ingredient	pphr
Isobutyl isoprene (0.7% unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.66
Tetramethyl thiuram disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day % Wgt. Chg.
			% Dia. Chg. mean		% Wgt. Chg. mean
R-22	4.5	4.5	3.9	[21.8/22.4]	22.1
R-32	0.5	0.7	1.0	[4.0/4.0]	4.0
R-124	1.0	1.5	3.2	[16.3/16.4]	16.4
R-134a	0.3		0.6	[3.0/2.7]	2.9
R-125	1.6	2.4	2.6	[8.2/7.2]	7.7
R-143a	0.7	0.6	1.3	[4.1/3.5]	3.8
R-152a	0.6	1.0	1.7	[7.6/6.4]	7.0
R-123	16.8	16.8	16.3	[90.2/90.2]	90.2
R-142b	4.7	6.1	6.2	[25.5/25.8]	25.7
R-134	-0.1	01	0.5	[2.9/2.8]	2.9
AB	23.4	-	[67.5/67.7] 67.6	[341/338]	339.0
MO	27.7	-	[72.1/65.7] 68.9	[386/335]	361.0
PEMA	1.6	-	[3.1/2.8] 3.0	[10.1/9.9]	10.0
PEBA	0.9	-	[2.0/2.4] 2.2	[6.9/7.5]	7.2
PPGD	-0.1	-	[0.4/-0.3] 0.1	[-0.1/-0.1]	-0.1
PPGBM	0.0	-	[0.2/0.2] 0.2	[-0.4/0.4]	0.0
MPG	3.2	-	[-2.1/-0.3] -1.2	[-0.1/-0.1]	-0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 7

Ingredient	pphr
Isobutyl isoprene (2.2% unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
Tetramethyl thiuram disulfide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day % Wgt. Chg.
			% Dia. Chg.	mean	mean
R-22	5.6	5.2	5.2		[22.5/22.5] 22.5
R-32	0.4	0.6	1.2		[4.0/4.0] 4.0
R-124	1.3	1.4	3.5		[17.1/16.7] 16.9
R-134a	0.2		0.6		[2.7/2.8] 2.8
R-125	2.1	2.6	3.0		[8.9/7.9] 8.4
R-143a	0.5	0.7	1.4		[4.2/4.3] 4.3
R-152a	1.1	1.4	1.9		[10.1/7.9] 9.0
R-123	16.6	16.5	16.3		[90.1/89.9] 90.0
R-142b	4.1	6.5	6.6		[26.7/25.8] 26.3
R-134	-0.1	0.6	0.5		[3.2/2.9] 3.1
AB	18.0	-	[54.6/55.2] 54.9		[254/253] 253.0
MO	24.7	-	[59.4/56.4] 57.9		[292/271] 282.0
PEMA	1.8	-	[3.0/3.0] 3.0		[10.0/10.7] 10.4
PEBA	0.1	-	[1.3/2.6] 2.0		[7.2/7.9] 7.6
PPGD	0.1	-	[0.5/-0.5] 0.0		[0.3/0.5] 0.4
PPGBM	0.2	-	[0.7/0.5] 0.6		[1.0/1.4] 1.2
MPG	-0.1	-	[-0.2/0.2] 0.0		[0.2/0.2] 0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 8

Ingredient	pphr
Isobutyl isoprene (2.2 % unsaturated)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
Tetramethyl thiuram disulfide	1
N330 Carbon Black	

50

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.
			mean	mean	
R-22	4.2	4.4	4.4	[15.0/15.1]	15.1
R-32	0.4	0.8	1.0	[2.8/2.6]	2.7
R-124	0.4	1.0	2.7	[19.5/18.2]	18.9
R-134a	0.1		0.4	[1.9/1.9]	1.9
R-125	0.6	1.5	1.9	[5.4/5.4]	5.4
R-143a	0.3	0.1	0.7	[2.7/2.3]	2.5
R-152a	0.6	0.4	1.6	[1.2/1.4]	1.3
R-123	11.9	11.9	12.0	[57.9/57.8]	57.9
R-142b	2.5	4.9	4.7	[17.3/17.3]	17.3
R-134	-0.2	0.1	0.4	[1.8/1.7]	1.8
AB	8.1	-	[35.9/35.3] 35.6	[129/126]	128.0
MO	10.7	-	[39.8/39.4] 39.6	[151/151]	151.0
PEMA	0.5	-	[2.1/2.3] 2.2	[6.7/6.6]	6.7
PEBA	0.5	-	[1.5/1.7] 1.6	[4.1/4.8]	4.5
PPGD	-0.1	-	[0.4/0.3] 0.4	[0.0/0.2]	0.1
PPGBM	0.2	-	[0.5/0.5] 0.5	[0.7/0.6]	0.7
MPG	0.1	-	[-0.1/-0.1] -0.1	[-0.1/-0.1]	-0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 9

Ingredient

pphr

Bromobutyl

100

Zinc Oxide

5

Stearic Acid

1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	5.3	5.6	5.3		[23.5/23.4]	23.5
R-32	0.8	1.1	1.1		[4.1/4.0]	4.1
R-124	1.7	2.4	4.1		[17.4/18.3]	17.9
R-134a	0.1		0.6		[3.1/2.8]	3.0
R-125	1.6	2.6	2.9		[8.5/7.6]	8.1
R-143a	0.4	0.4	1.1		[4.3/4.4]	4.4
R-152a	0.6	1.6	1.9		[6.9/6.1]	6.5
R-123	18.7	18.9	18.8		[102/102]	102.0
R-142b	4.9	6.7	6.5		[26.9/26.3]	26.6
R-134	0.3	0.2	0.2		[2.9/2.7]	2.8
AB	30.3	-	[85.9/77.2]	81.6	[523/447]	485.0
MO	37.8	-	[86.2/86.2]	86.2	[521/509]	515.0
PEMA	1.6	-	[5.9/6.0]	6.0	[21.2/21.5]	21.4
PEBA	1.1	-	[3.3/4.0]	3.7	[10.9/12.9]	11.9
PPGD	0.6	-	[0.8/1.5]	1.2	[5.1/5.3]	5.2
PPGBM	0.0	-	[1.0/0.8]	0.9	[4.0/4.1]	4.1
MPG	0.1	-	[0.2/-0.1]	0.1	[1.1/1.1]	1.1

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 10

Ingredient

pphr

Bromobutyl

100

Zinc Oxide

5

Stearic Acid

1

N330 Carbon black

40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	3.9	3.9	3.8		[17.0/16.8]	16.9
R-32	0.3	0.2	0.5		[3.5/3.3]	3.4
R-124	0.8	1.4	2.5		[12.5/12.6]	12.6
R-134a	0.2		0.4		[1.6/1.9]	1.8
R-125	1.3	2.0	2.7		[7.9/7.1]	7.5
R-143a	0.5	0.4	0.9		[3.1/2.7]	2.9
R-152a	0.4	0.7	1.2		[4.6/5.0]	4.8
R-123	14.3	14.4	14.4		[71.6/71.8]	71.7
R-142b	2.2	5.3	5.6		[19.2/19.2]	19.2
R-134	-0.1	0.4	-0.2		[2.1/2.4]	2.3
AB	15.5	-	[47.1/47.6]	47.4	[187/190]	188.0
MO	19.2	-	[52.2/50.9]	51.6	[229/225]	227.0
PEMA	1.5	-	[4.0/3.9]	4.0	[12.6/12.0]	12.5
PEBA	0.2	-	[2.0/2.2]	2.1	[8.0/6.4]	7.1
PPGD	0.5	-	[1.4/1.1]	1.3	[3.2/3.2]	3.2
PPGBM	0.5	-	[1.0/0.6]	0.8	[3.0/2.7]	2.9
MPG	-0.1	-	[0.3/0.2]	0.3	[0.8/0.7]	0.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 11

Ingredient

pphr

Chlorobutyl
Zinc Oxide
Stearic Acid

100
5
1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	5.8	6.1	5.7		[26.2/25.5]	25.9
R-32	0.6	0.7	1.2		[4.5/4.6]	4.6
R-124	1.3	2.0	3.6		[19.7/17.6]	18.7
R-134a	0.1	0.3	0.5		[2.8/2.6]	2.7
R-125	1.8	2.1	2.5		[8.1/7.2]	7.7
R-143a	0.5	0.7	1.3		[4.0/3.8]	3.9
R-152a	0.8	1.1	1.9		[6.7/6.6]	6.7
R-123	18.2	18.2	18.5		[32.9/34.1]	33.5
R-142b	4.9	6.7	7.0		[27.9/28.1]	28.0
R-134	-0.2	0.1	-0.1		[3.0/2.7]	2.9
AB	29.9	-	[62.7/61.3]	62.0	[304/292]	298.0
MO	38.3	-	[69.1/69.0]	69.0	[385/371]	378.0
PEMA	1.4	-	[4.2/4.1]	4.2	[15.0/14.5]	15.0
PEBA	1.0	-	[3.4/3.7]	3.6	[13.0/13.1]	13.1
PPGD	0.3	-	[1.3/1.4]	1.3	[4.4/4.4]	4.4
PPGBM	-0.2	-	[0.6/0.7]	0.7	[3.1/3.3]	3.2
MPG	0.5	-	[0.1/0.1]	0.1	[1.1/1.1]	1.1

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 12

Ingredient	pphr
Chlorobutyl	100
Zinc Oxide	5
Stearic Acid	1
N330 Carbon Black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	5.0	5.0	4.0	[26.0/15.0]	25.2	
R-32	0.3	0.3	0.4	[3.0/3.0]	3.0	
R-124	1.0	2.0	3.0	[13.2/13.2]	13.2	
R-134a	0.1	0.0	0.3	[2.0/2.0]	2.0	
R-125	1.0	1.0	2.0	[5.0/4.0]	4.0	
R-143a	0.2	0.2	1.0	[2.0/2.5]	2.3	
R-152a	0.4	0.6	1.1	[5.1/4.9]	5.0	
R-123	13.8	13.6	13.6	[73.2/73.4]	73.3	
R-142b	3.7	4.9	5.3	[20.0/20.1]	20.0	
R-134	-0.1	0.1	-0.6	[2.5/2.0]	2.3	
AB	17.6	-	[39.5/38.6]	39.1	[151/145]	148.0
MO	23.4	-	[45.1/43.9]	44.5	[186/183]	184.0
PEMA	1.0	-	[3.3/3.4]	3.3	[10.4/10.5]	10.5
PEBA	1.1	-	[2.7/3.2]	2.9	[8.7/9.3]	9.0
PPGD	0.2	-	[0.8/0.5]	0.6	[2.7/2.4]	2.6
PPGBM	-0.3	-	[0.2/0.3]	0.3	[2.3/2.3]	2.3
MPG	-0.3	-	[0.3/-0.1]	0.1	[0.9/1.0]	1.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 13

Ingredient

pphr

SBR (23.5 % Styrene Content)

100

Zinc Oxide

3

Sulfur

1.75

Stearic Acid

1

N-t-butyl-2-benzothiazyl sulfenamide

1

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.		% Wgt. Chg.	
				mean		mean
R-22	9.9	10.0	9.8		[41.1/39.5]	40.3
R-32	2.0	1.6	2.0		[7.0/6.6]	6.8
R-124	5.9	5.4	4.1		[22.5/22.5]	22.5
R-134a	1.1		1.0		[5.0/5.0]	5.0
R-125	3.1	3.8	3.6		[10.8/10.0]	10.4
R-143a	1.4	1.5	1.5		[5.2/5.2]	5.2
R-152a	3.0	3.1	2.8		[11.1/10.6]	10.9
R-123	41.4	41.2	40.8		[271/271]	271.0
R-142b	7.8	7.5	7.3		[31.1/30.3]	30.7
R-134	1.9	2.0	1.4		[7.3/7.5]	7.4
AB	29.7	-	[43.6/42.3]	43.0	[175/171]	173.0
MO	32.5	-	[44.5/44.1]	44.3	[186/186]	186.0
PEMA	16.3	-	[22.9/22.6]	22.8	[85.6/84.7]	85.2
PEBA	9.4	-	[16.0/16.1]	16.1	[57.0/56.5]	56.8
PPGD	1.6	-	[1.2/1.8]	1.5	[5.9/5.5]	5.7
PPGBM	5.9	-	[10.0/9.2]	9.6	[29.4/29.5]	29.5
MPG	1.6	-	[2.5/2.7]	2.6	[8.1/8.3]	8.2

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 14

Ingredient	pphr
SBR 1502 (23.5 % Styrene content)	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
N-t-butyl-2-benzothiazyl sulfenamide	1
N330 Carbon Black	50

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	7.6	7.1	7.1	[26.9/27.1] 27.0
R-32	1.2	1.2	1.1	[4.5/4.4] 4.5
R-124	3.4	3.4	3.1	[15.0/15.3] 15.2
R-134a	0.9		0.6	[3.3/3.7] 3.5
R-125	2.0	2.1	2.1	[7.0/6.5] 6.8
R-143a	0.9	1.1	0.9	[3.7/3.6] 3.7
R-152a	2.3	2.1	2.0	[6.4/6.6] 6.5
R-123	24.3	24.2	24.9	[138/138] 138.0
R-142b	6.0	6.0	5.9	[20.1/20.0] 20.1
R-134	1.2	1.3	1.1	[4.6/4.8] 4.7
AB	15.7	-	[24.0/24.2] 24.1	[81.9/81.2] 81.6
MO	17.4	-	[24.2/23.7] 24.0	[88.8/88.6] 88.7
PEMA	8.8	-	[13.2/13.2] 13.2	[45.5/45.1] 45.3
PEBA	4.2	-	[9.2/9.2] 9.2	[31.3/30.8] 31.1
PPGD	1.1	-	[2.1/1.4] 1.8	[5.0/4.8] 4.9
PPGBM	3.3	-	[5.5/5.4] 5.5	[18.8/18.0] 18.9
MPG	1.1	-	[1.8/1.8] 1.8	[5.6/5.6] 5.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 15

Ingredient

pphr

SBR (Medium Styrene) Content	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
N-t-butyl-2-benzothiazyl sulfenamide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	10.2	11.3	11.4		[43.8/41.9]	42.9
R-32	1.3	1.2	1.2		[7.8/7.4]	7.6
R-124	4.4	4.2	3.7		[24.0/23.1]	23.6
R-134a	1.9	1.6	1.7		[7.5/7.4]	7.5
R-125	2.3	2.7	1.9		[10.1/9.8]	10.0
R-143a	1.7	1.6	1.6		[7.1/6.9]	7.0
R-152a	2.7	2.4	3.0		[10.2/10.0]	10.1
R-123	43.5	44.6	45.7		[316/313]	315.0
R-142b	8.3	8.6	7.6		[-0.7/-0.9]	-0.8
R-134	1.2	1.3	1.2		[8.5/8.1]	8.3
AB	34.0	-	[43.5/61.3]	52.4	[179/292]	236.0
MO	32.7	-	[42.1/41.1]	41.6	[179/176]	178.0
PEMA	14.0	-	[20.3/20.2]	20.3	[78.0/78.0]	78.0
PEBA	11.0	-	[16.9/47.0]	32.0	[64.5/62.2]	63.4
PPGD	2.6	-	[3.4/3.2]	3.3	[12.7/12.1]	12.4
PPGBM	5.2	-	[8.5/7.7]	8.1	[28.5/28.1]	28.3
MPG	2.2	-	[2.8/2.6]	2.7	[10.0/10.2]	10.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

M/G - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 16

Ingredient	pphr
SBR (High Styrene) Content	100
Zinc Oxide	3
Stearic Acid	1
Sulfur	1.75
N-t-butyl-2-benzothiazyl sulfenamide	1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	10.7	10.6	10.2	[44.7/42.5] 43.6
R-32	2.3	2.3	2.3	[14.0/0.4] 7.2
R-124	5.2	5.1	5.1	[22.4/22.4] 22.4
R-134a	2.1	1.9	1.7	[7.6/6.7] 7.2
R-125	2.9	3.0	2.8	[9.2/8.8] 9.0
R-143a	1.4	1.6	1.4	[-0.4/-0.4] -0.4
R-152a	3.8	3.4	3.5	[10.3/10.1] 10.2
R-123	52.9	53.1	52.6	[380/393] 386.0
R-142b	7.9	7.8	7.8	[31.0/30.1] 30.5
R-134	1.6	1.5	1.7	[7.5/7.6] 7.6
AB	38.6	-	[59.3/59.0] 59.2	[275/271] 273
MO	36.3	-	[53.4/52.5] 53.0	[268/255] 261.0
PEMA	15.8	-	[32.0/28.2] 30.1	[141/112] 127.0
PEBA	12.4	-	[20.9/22.0] 21.5	[83.6/82.6] 83.1
PPGD	2.1	-	[3.6/3.2] 3.4	[11.3/11.4] 11.4
PPGBM	5.9	-	[11.1/11.0] 11.1	[37.3/37.0] 37.2
MPG	2.4	-	[3.7/3.0] 3.4	[11.0/11.0] 11.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 17

Ingredient	pphr
Very High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	47.8	47.5	47.6	[255/238] 247.0
R-32	8.5	8.5	8.4	[30.0/29.3] 29.7
R-124	39.6	39.7	40.2	[257/241] 249.0
R-134a	2.0	3.0	4.9	[20.7/20.4] 20.6
R-125	0.8	0.0	1.7	[7.4/9.7] 8.6
R-143a	0.2	0.4	0.9	[3.2/3.4] 3.3
R-152a	7.8	7.9	7.9	[24.9/24.3] 24.6
R-123	78.5	79.2	77.5	[669/664] 666.0
R-142b	3.8	5.6	7.3	[28.8/28.7] 28.8
R-134	21.7	22.0	21.4	[111/109] 110.0
AB	0.2	-	[0.2/-0.1] 0.1	[0.2/0.2] 0.2
MO	-0.2	-	[0.3/0.3] 0.3	[1.5/1.6] 1.6
PEMA	0.8	-	[1.6/1.9] 1.7	[5.0/5.3] 5.2
PEBA	0.4	-	[1.0/1.1] 1.0	[3.1/3.6] 3.4
PPGD	1.0	-	[2.0/2.0] 2.0	[5.6/5.7] 5.7
PPGBM	0.4	-	[0.3/0.1] 0.2	[0.3/0.5] 0.4
MPG	0.4	-	[-0.4/-0.3] -0.4	[-0.2/-0.1] -0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 18

Ingredient	pphr
High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	51.4	50.8	51.4		[275/260]	268.0
R-32	8.3	8.3	8.3		[30.0/29.3]	29.7
R-124	45.4	45.3	45.9		[289/274]	282.0
R-134a	2.5	4.1	5.1		[22.0/21.9]	22.0
R-125	1.5	2.0	3.9		[16.2/15.9]	16.1
R-143a	0.6	1.0	2.0		[5.8/5.8]	5.8
R-152a	8.6	8.7	8.8		[27.5/27.3]	27.4
R-123	83.0	83.4	83.7		[720/713]	716.0
R-142b	6.5	8.6	8.7		[34.2/34.4]	34.3
R-134						
AB	0.4	-	[0.2/0.2]	0.2	[0.7/0.9]	0.8
MO	0.4	-	[0.7/0.9]	0.8	[2.5/2.7]	2.6
PEMA	1.6	-	[3.8/3.2]	3.5	[10.9/10.4]	10.7
PEBA	1.0	-	[2.1/2.6]	2.4	[6.3/7.2]	6.7
PPGD	1.5	-	[3.2/2.7]	2.9	[9.7/8.3]	9.0
PPGBM	0.3	-	[0.4/0.2]	0.3	[1.0/1.1]	1.1
MPG	0.3	-	[-0.2/-0.3]	-0.2	[0.1/0.0]	0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 19

Ingredient	pphr
Medium ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day % Wgt. Chg.
			% Dia. Chg.	mean	mean
R-22	49.8	49.8	50.4		[262/244] 253.0
R-32	7.7	7.7	7.8		[26.8/26.0] 26.4
R-124	46.2	46.1	45.8		[311/284] 298.0
R-134a	5.1	5.8	5.7		[25.0/23.7] 24.4
R-125	3.5	5.1	6.2		[23.5/23.1] 23.3
R-143a	1.4	2.3	2.7		[9.0/9.0] 9.0
R-152a	8.8	8.9	8.7		[28.4/27.8] 28.1
R-123	94.2	94.1	94.4		[875/883] 879.0
R-142b	11.6	11.6	11.6		[47.2/46.8] 47.0
R-134	14.9	14.5	14.6		[75.5/74.8] 75.2
AB	0.9	-	[1.7/1.9] 1.8		[5.1/4.9] 5.0
MO	1.3	-	[2.6/2.7] 2.7		[8.3/8.7] 8.5
PEMA	6.4	-	[9.9/9.7] 9.8		[33.2/33.2] 33.2
PEBA	3.8	-	[7.7/7.7] 7.7		[25.4/25.6] 25.5
PPGD	5.8	-	[8.0/7.9] 7.9		[25.6/25.4] 25.5
PPGBM	1.3	-	[2.0/1.8] 1.9		[5.9/5.8] 5.9
MPG	0.5	-	[0.7/0.7] 0.7		[2.6/2.9] 2.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 20

Ingredient	pphr
Low ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
Magnesium Carbonate Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	35.6	35.1	35.4	[180/174] 177.0
R-32	6.2	6.1	6.1	[21.6/21.0] 21.3
R-124	31.0	31.2	29.9	[199/187] 193.0
R-134a	4.5	4.3	4.3	[19.2/18.8] 19.0
R-125	5.0	5.3	5.2	[21.9/21.4] 21.7
R-143a	2.8	3.2	3.4	[11.9/11.1] 11.5
R-152a	7.4	8.1	7.4	[27.3/27.0] 27.2
R-123	73.9	71.3	73.2	[739/755] 747.0
R-142b	13.8	14.1	14.0	[59.9/58.9] 59.4
R-134	9.4	9.1	8.9	[45.4/44.1] 44.8
AB	4.8	-	[6.9/7.1] 7.0	[21.0/22.0] 21.5
MO	4.2	-	[7.0/8.4] 7.7	[26.9/26.9] 26.9
PEMA	21.5	-	[23.5/24.7] 24.1	[98.4/98.9] 98.6
PEBA	13.1	-	[18.9/19.2] 19.0	[72.0/72.1] 72.1
PPGD	11.0	-	[11.1/11.4] 11.3	[39.9/39.9] 39.9
PPGBM	4.0	-	[7.2/7.6] 7.4	[23.7/23.8] 23.7
MPG	2.3	-	[4.3/3.9] 4.1	[13.9/14.3] 14.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 21

Ingredient	pphr
Low ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
MgCO ₃ Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	25.8	23.0	22.0		[121/115]	118.0
R-32	4.3	4.5	4.2		[15.9/15.7]	15.8
R-124	20.3	23.5	23.5		[110/106]	108.0
R-134a	3.3	3.4	3.5		[15.5/15.4]	15.5
R-125	3.0	3.8	3.4		[15.8/15.6]	15.7
R-143a	1.6	1.7	1.4		[8.0/7.9]	8.0
R-152a	5.6	5.3	5.2		[19.6/19.0]	19.3
R-123	42.5	41.9	40.9		[352/362]	357.0
R-142b	8.5	9.0	9.1		[41.3/40.5]	40.9
R-134	7.3	7.3	7.0		[33.9/33.3]	33.6
AB	3.4	-	[4.8/4.4]	4.6	[13.7/14.1]	13.9
MO	2.9	-	[5.3/5.0]	5.2	[18.2/18.3]	18.3
PEMA	7.3	-	[15.0/14.0]	14.5	[57.0/57.0]	57.0
PEBA	5.8	-	[12.2/11.6]	11.9	[46.5/46.4]	46.5
PPGD	4.7	-	[6.1/7.1]	6.6	[26.6/27.1]	26.9
PPGBM	2.1	-	[4.5/4.4]	4.5	[16.0/15.6]	15.8
MPG	1.4	-	[2.5/2.9]	2.7	[9.7/9.8]	9.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 22

Ingredient	pphr
Very High ACN Nitrile	100
Zinc Oxide	3
Stearic Acid	1
MgCO ₃ Coated Sulfur	1.5
N-t-butyl-2-benzothiazyl sulfenamide	0.7
N330 Carbon Black	35

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	31.5	31.6	31.7		[157/165]	161.0
R-32	6.3	6.4	6.2		[22.4/22.2]	22.3
R-124	27.9	29.2	28.7		[136/138]	137.0
R-134a	1.2	2.5	4.2		[15.7/15.8]	15.8
R-125	0.4	0.8	1.6		[6.8/7.0]	6.9
R-143a	0.4	0.3	0.8		[2.8/2.3]	2.6
R-152a	5.6	5.9	5.6		[18.3/18.4]	18.4
R-123	49.3	49.4	49.7		[388/391]	390.0
R-142b	1.9	4.2	5.5		[21.1/21.3]	21.2
R-134	16.0	15.6	16.5		[80.4/78.6]	79.5
AB	0.0	-	[0.1/0.1]	0.1	[0.3/0.3]	0.3
MO	0.0	-	[0.4/0.5]	0.5	[1.1/1.2]	1.2
PEMA	0.1	-	[0.8/0.8]	0.8	[3.0/2.5]	2.8
PEBA	1.3	-	[5.6/3.8]	4.7	[15.3/13.1]	14.2
PPGD	1.0	-	[2.2/2.0]	2.1	[6.4/6.6]	6.5
PPGBM	0.2	-	[0.2/0.1]	0.2	[0.3/0.3]	0.3
MPG	0.0	-	[0.0/0.0]	0.0	[-0.4/-0.2]	-0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 23

Ingredient	pphr
38 % ACN Hydrogenated Nitrile	100
Zinc Oxide	5
Stearic Acid	1
Magnesium oxide	10
2,5-dimethyl-2,5-di(t-butyl-peroxy) hexane	10
Ricon 153-D	6.5

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	33.7	34.1	34.2		[171/159]	165.0
R-32						
R-124	31.8	32.2	31.8		[189/181]	185.0
R-134a	4.2	4.9	5.0		[23.3/23.3]	23.3
R-125	4.4	7.6	7.1		[30.0/29.2]	29.6
R-143a	0.7	0.8	1.3		[3.6/3.5]	3.6
R-152a	7.7	6.8	6.8		[22.8/23.1]	23.0
R-123	45.8	44.0	45.2		[314/317]	316.0
R-142b	9.7	10.6	10.8		[44.1/44.0]	44.1
R-134						
AB	0.3	-	[1.6/1.8]	1.7	[5.5/6.0]	5.8
MO	1.2	-	[2.8/2.6]	2.7	[10.9/9.6]	10.1
PEMA	0.4	-	[4.2/5.3]	4.8	[17.6/17.9]	17.8
PEBA	1.3	-	[5.6/3.8]	4.7	[5.7/7.6]	6.7
PPGD		-				
PPGBM	-0.1	-	[0.4/0.3]	0.4	[3.4/3.1]	3.3
MPG	0.0	-	[-0.1/0.1]	0.0	[2.1/1.2]	1.7

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 24

Ingredient	pphr
38 % ACN Hydrogenated Nitrile	100
Zinc Oxide	5
Stearic Acid	1
MgCO ₃ Coated Sulfur	1.5
TMTM	0.3
MBTS	1.5
N774 Carbon Black	40

Swell Data.

Test Fluid	24 Hour	72 Hour	14 Day	14 Day
	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.	mean
R-22	68.4	66.4	66.0	[320/208] 264.0
R-32	6.3	6.2	6.0	[20.4/20.5] 20.5
R-124	69.9	68.9		[338/328] 333.0
R-134a	4.7	5.3	5.5	[21.1/21.2] 21.2
R-125	5.2	6.7	6.7	[26.0/26.1] 26.1
R-143a	1.2	2.1	2.4	[8.0/15.2] 11.6
R-152a	7.1	6.9	7.0	[22.0/22.0] 22.0
R-123	122	121	115	[1293/1301] 1297
R-142b	10.8	10.6	11.0	[42.1/40.8] 41.45
R-134	15.3	15.5	15.4	[70.8/69.9] 70.4
AB	1.0	-	[1.9/1.9] 1.9	[4.9/4.9] 4.9
MO	1.3	-	[3.3/3.0] 3.2	[8.8/8.7] 8.8
PEMA	3.4	-	[6.9/6.8] 6.9	[16.0/28.1] 22.1
PEBA	2.0	-	[5.7/7.6] 6.7	[18.4/18.4] 18.4
PPGD	-0.6	-	[0.1/2.7] 1.4	[8.6/8.5] 8.6
PPGBM	-1.4	-	[-1.3/0.6] -0.4	[1.6/1.7] 1.7
MPG	1.0	-	[-0.6/-1] -0.4	[0.2/0.4] 0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 25

Ingredient	pphr
45 % ACN Hydrogenated Nitrile	100
Zinc Oxide	5
Stearic Acid	1
2,5-dimethyl-2,5-di(t-butyl-peroxy) hexane	10
Ricon 153-D	6.5

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	41.9	41.9	42.0	[215/23] 209.0
R-32				
R-124	39.5	39.3	39.1	[260/246] 253.0
R-134a	4.3	5.4	5.2	[25.3/25.8] 25.6
R-125	4.0	6.2	6.2	[29.0/30.0] 29.5
R-143a	1.3	1.6	2.1	[7.9/7.7] 7.8
R-152a	7.8	8.0	7.8	[26.6/25.6] 26.1
R-123	56.1	56.9	57.2	[442/449] 446.0
R-142b	9.9	10.2	10.1	[42.9/42.4] 42.6
R-134				
AB	0.4	-	[0.9/0.3] 0.6	[3.5/2.5] 3.0
MO	0.4	-	[1.6/1.9] 1.8	[7.8/7.5] 7.7
PEMA	1.4	-	[4.5/3.4] 4.0	[12.8/12.3] 12.6
PEBA	1.0	-	[2.6/3.3] 3.0	[9.5/11.2] 10.4
PPGD	1.5	-	[2.6/2.2] 2.4	[7.0/7.3] 7.2
PPGBM	-1.5	-	[-0.9/0.4] -0.3	[2.0/2.8] 2.4
MPG	-0.3	-	[-0.6/-0.2] -0.4	[0.6/0.4] 0.5

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 26

Ingredient	pphr
45 % ACN Hydrogenated Nitrile	100
Zinc Oxide	5
Stearic Acid	1
2,5-dimethyl-2,5-di(t-butyl-peroxy) hexane	10
Ricon 153-D	6.5
N774 Carbon black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	24.3	25.3	25.8		[130/123]	127.0
R-32						
R-124	23.2	23.6	23.7		[145/129]	137.0
R-134a	3.1	3.2	3.1		[16.4/16.1]	16.3
R-125	3.6	4.6	4.8		[22.7/23.2]	23.0
R-143a	0.6	0.6	0.6		[3.4/3.5]	3.5
R-152a	6.1	4.8	5.3		[16.3/16.3]	16.3
R-123	32.4	31.7	35.2		[211/216]	213.0
R-142b	5.6	6.7	6.6		[27.5/27.4]	27.4
R-134						
AB	0.4	-	[0.3/0.5]	0.4	[1.2/0.9]	1.0
MO	0.1	-	[1.0/0.5]	0.8	[3.8/3.1]	3.5
PEMA	0.1	-	[2.2/2.7]	2.5	[8.2/9.2]	8.7
PEBA	0.5	-	[2.8/2.1]	2.5	[7.3/7.0]	7.2
PPGD	0.5	-	[1.0/1.1]	1.1	[4.2/4.2]	4.2
PPGBM	-0.6	-	[-1.0/-0.4]	-0.7	[-.07/-0.5]	-0.7
MPG	-0.4	-	[-1.1/-0.2]	-0.7	[-1.7/-1.9]	-1.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 27

Ingredient

pphr

Fluorinated rubber

100

Magnesium oxide

15

N,N'-dicinnamylidene-1,6-hexanediamine

3

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.		
			mean		mean	
R-22	34.2	34.2	33.2	[84.4/81.5]	83.0	
R-32						
R-124	27.9	29.6	28.9	[91.0/88.0]	89.5	
R-134a	29.5	29.8	29.3	[68.2/67.3]	67.8	
R-125	11.0	11.8	11.7	[31.5/31.2]	31.4	
R-143a	17.1	14.3	13.6	[28.6/28.0]	28.3	
R-152a	39.0	39.4	39.1	[83.8/79.3]	81.6	
R-123	34.8	31.8	31.6	[105/103]	104.0	
R-142b	32.6	32.6	31.8	[82.4/77.9]	80.1	
R-134						
AB	0.7	-	[0.1 0.1]	0.1	[0.4/0.5]	0.5
MO	-1.1	-	[-1.4 0.2]	-0.6	[0.6/0.5]	0.6
PEMA	1.3	-	[3.3 3.3]	3.3	[6.6/6.0]	6.3
PEBA	2.2	-	[8.1 8.9]	8.5	[16.5/16.7]	16.6
PPGD	1.0	-	[0.8 1.2]	1.0	[1.4/1.7]	1.6
PPGBM	-0.2	-	[0.1 0.3]	0.2	[0.7/0.9]	0.8
MPG	0.1	-	[0.1]		[0.7]	

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 28

Ingredient	pphr
Fluoroelastomer	100
Magnesium oxide	15
N,N'-dicinnamylidene-1,6-hexanediamine	3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Wgt. Chg.	14 Day
R-22	37.2	36.4	35.6	[99.6/94.0] 96.8
R-32				
R-124	38.6	38.4	37.8	[125/120] 123
R-134a	29.2	29.9	29.4	[84.1/81.5] 82.8
R-125	15.1	15.2	15.2	[42.0/41.6] 41.8
R-143a	16.9	16.6	17.1	[36.5/36.2] 36.4
R-152a	41.0	40.7	40.1	[92.9/82.8] 87.9
R-123	37.5	37.9	37.4	[131/134] 133.0
R-142b	38.6	39.3	38.7	[102/96.6] 99.1
R-134				
AB	0.5	-	[0.3/0.1] 0.2	[0.5/0.3] 0.4
MO	-0.5	-	[0.2/0.1] 0.1	[0.5/0.4] 0.5
PEMA	0.5	-	[1.0/0.9] 1.0	[2.3/2.2] 2.3
PEBA	0.8	-	[2.1/1.9] 2.0	[3.5/4.0] 3.8
PPGD	-0.5	-	[1.3/0.6] 1.0	[1.1/1.2] 1.2
PPGBM	-0.1	-	[-0.1/-1.0] -0.5	[1.0/1.1] 1.1
MPG	-0.7	-	[-0.6/0.9] 0.2	[0.7/0.6] 0.7

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 29

Ingredient	pphr
Fluoroclastomer	100
Litharge (Sublimed)	3
Triallyl Isocyanurate	3
2,5-Dimethyl-2,5-bis(t-butylperoxy) hexane	3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Wgt. Chg.	14 Day
R-22	36.2	35.9	35.5	[91.2/83.8] 87.5
R-32	19.5	19.6	19.6	[35.8/32.5] 34.2
R-124	39.8	40.4	39.9	[125/120] 122.0
R-134a	30.4	30.4	30.2	[79.0/77.0] 78.0
R-125	19.8	19.7	19.6	[49.9/48.7] 49.3
R-143a	20.7	20.7	20.8	[38.4/37.8] 38.1
R-152a	34.8	35.0	34.4	[62.7/58.9] 60.8
R-123	35.7	37.0	37.8	[121/121] 121.0
R-142b	37.9	38.0	37.6	[95.2/91.1] 93.2
R-134	32.4	32.3	32.3	[87.0/84.9] 86.0
AB	0.8	-	[0.2/0.0] 0.1	[0.2/0.1] 0.2
MO	-0.6	-	[-0.2/0.8] 0.3	[0.2/0.2] 0.2
PEMA	1.0	-	[0.7/0.7] 0.7	[1.1/1.1] 1.1
PEBA	0.8	-	[1.3/0.9] 1.1	[1.6/1.7] 1.6
PPGD	1.0	-	[0.5/1.0] 0.7	[0.8/0.7] 0.7
PPGBM	0.5	-	[0.2/0.0] 0.1	[0.4/0.3] 0.3
MPG	0.1	-	[-0.3/0.1] -0.1	[0.2/0.2] 0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 30

Ingredient	pphr
Fluoroelastomer	100
Litharge (Sublimed)	3
Triallyl Isocyanurate	3
2,5-Dimethyl-2,5-bis (t-butylperoxy) hexane	3
N330 Carbon Black	30

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	22.0	22.2	22.5		[57.8/56.4]	57.1
R-32	13.6	12.7	13.7		[27.0/25.6]	26.3
R-124	24.1	23.4	24.0		[73.7/68.4]	71.1
R-134a	19.2	18.8	18.2		[50.0/47.2]	48.6
R-125	13.4	13.5	13.3		[36.5/35.8]	36.2
R-143a	13.8	14.2	14.0		[27.9/26.9]	27.4
R-152a	21.5	21.9	21.5		[41.8/40.2]	41.0
R-123	22.6	22.9	24.3		[70.7/58.5]	64.6
R-142b	23.2	23.6	23.0		[56.2/52.5]	54.4
R-134	19.9	19.1	21.1		[54.0/53.0]	53.5
AB	0.3	-	[0.1/0.1]	0.1	[0.2/0.3]	0.3
MO	-0.1	-	[0.5/0.3]	0.4	[0.3/0.3]	0.3
PEMA	0.4	-	[1.0/0.4]	0.7	[1.0/1.0]	1.0
PEBA	0.3	-	[1.0/0.5]	0.8	[1.5/1.6]	1.6
PPGD	0	-	[0.4/0.5]	0.5	[0.9/0.9]	0.9
PPGBM	0.2	-	[0.3/0.2]	0.2	[0.4/0.4]	0.4
MPG	0.1	-	[0.3/0.4]	0.3	[0.2/0.2]	0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 31

Ingredient

pphr

Fluoroelastomer	100
Litharge (Sublimed)	1.8
Triallyl Isocyanurate	1.8
2,5-Dimethyl-2,5-bis(t-butylperoxy) hexane	1.8

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	25.8	25.6	25.9		71.6/69.1	70.4
R-32	17.4	17.5	16.7		[34.2/34.0]	34.1
R-124	20.8	21.1	21.5		[64.0/63.5]	63.8
R-134a	15.7	15.6	16.2		43.2/42.2	42.7
R-125	5.8	7.6	8.6		22.0/22.0	22.0
R-143a	9.9	10.0	10.2		22.7/22.4	22.6
R-152a	27.9	27.2	27.0		[59.3/57.0]	58.2
R-123	27.8	27.3	29.1		106/108	107
R-142b	26.3	25.9	25.1		67.1/66.9	67.0
R-134	22.7	22.8	22.3		[67.0/66.1]	66.6
AB	-2.6	-	[-0.1/1.4]	0.2	[0.3/0.3]	0.3
MO	0.0	-	[0.6/0.3]	0.5	[0.4/0.3]	0.4
PEMA	10.8	-	[31.5/31.5]	31.5	[50.2/43.9]	47.1
PEBA	14.6	-	[35.6/28.7]	32.2	[86.0/66.8]	76.4
PPGD	1.5	-	[4.5/4.9]	4.7	[9.8/9.6]	9.2
PPGBM	0.1	-	[0.4/0.1]	0.3	[1.0/1.1]	1.1
MPG	0.1	-	[0.5/0.4]	0.5	[1.0/0.8]	0.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 32

Ingredient	pphr
Fluoroelastomer	100
Magnesium oxide	15
N,N'-dicinnamylidene-1,6-hexanediamine	3

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.		% Wgt. Chg.	
				mean		mean
R-22	24.8	24.9	23.5		[87.0/81.0]	84.0
R-32						
R-124	19.3	20.1	19.7		[81.0/78.0]	79.5
R-134a	12.6	13.2	13.0		[45.0/44.5]	44.8
R-125	5.2	6.0	6.5		[22.3/22.7]	22.5
R-143a	7.6	7.5	8.1		[22.2/22.0]	22.1
R-152a	26.1	26.8	25.4		[70.0/66.5]	68.3
R-123	34.1	36.8	36.0		[169/166]	168.0
R-142b	29.3	27.3	28.9		[91.1/80.2]	85.6
R-134						
AB	0.5	-	[0.7/0.1]	0.4	[1.5/1.3]	1.4
MO	0.5	-	[1.5/0.4]	0.9	[2.1/1.6]	1.9
PEMA	9.9	-	[50.2/43.9]	47.1	[197/167]	182.0
PEBA	8.9	-	[48.8/45.7]	47.3	[171/143]	157.0
PPGD	1.3	-	[3.5/3.1]	3.3	[9.5/9.0]	9.3
PPGBM	1.0	-	[0.9/0.7]	0.8	[3.0/3.3]	3.2
MPG	-0.1	-	[0.8/0.8]	0.8	[2.5/3.2]	2.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 33

Ingredient	pphr
Fluoroelastomer	100
Magnesium oxide	15
N,N'-dicinnamylidene-1,6-hexanediamine	3
IRB6 (Carbon black)	30

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	7.0	7.0	6.5		[22.8/20.8]	21.8
R-32						
R-124	4.5	5.3	5.0		[24.1/29.2]	26.7
R-134a	3.4	4.6	4.1		[18.2/17.3]	17.8
R-125	2.7	4.0	4.8		[14.7/13.2]	14.0
R-143a	4.5	3.3	3.0		[12.8/11.9]	12.4
R-152a	4.9	6.1	6.0		[16.7/16.6]	16.7
R-123	2.4	5.8	6.5		[23.6/28.8]	26.2
R-142b	5.5	6.8	5.7		[21.3/18.0]	19.7
R-134						
AB	0.4	-	[0.2/0.2]	0.2	[0.9/1.0]	1.0
MO	-0.1	-	[-0.1/-0.1]	-0.1	[0.7/0.7]	0.7
PEMA	0.8	-	[6.7/5.4]	6.1	[16.8/17.6]	17.2
PEBA	2.1	-	[6.0/5.9]	6.0	[20.3/-30.0]	-5.2
PPGD	0.4	-	[2.1/1.7]	1.9	[5.5/5.5]	5.5
PPGBM	-0.1	-	[0.2/1.6]	0.9	[1.3/1.3]	1.3
MPG	0.5	-	[1.0/0.8]	0.9	[1.6/1.5]	1.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 34

Ingredient	pphr
Epichlorohydrin Homopolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	12.3	21.1	12.3	[38.9/38.4] 38.7
R-32	4.7	4.3	4.2	[11.9/11.8] 11.9
R-124	0.8	1.7	3.4	[11.7/11.3] 11.5
R-134a	0.3	0.9	1.3	[4.2/4.3] 4.3
R-125	0.0	0.1	0.1	[1.3/1.4] 1.3
R-143a	0.2	0.4	0.9	[2.6/2.7] 2.7
R-152a	4.3	4.9	4.8	[11.9/11.9] 11.9
R-123	16.4	17.5	17.1	[68.0/68.0] 68.0
R-142b	2.3	4.3	5.0	[14.4/14.3] 14.3
R-134	1.3	2.8	3.5	[12.7/12.0] 12.4
AB	1.6	-	[0.2/0.3] 0.3	[0.5/0.5] 0.5
MO	0.6	-	[1.2/0.7] 1.0	[2.6/2.6] 2.6
PEMA	13.4	-	[26.8/26.8] 26.8	[73.0/72.7] 72.9
PEBA	7.7	-	[17.2/17.5] 17.4	[44.0/45.0] 44.5
PPGD	9.0	-	[18.2/17.9] 18.1	[46.4/46.6] 46.5
PPGBM	0.4	-	[2.0/2.0] 2.0	[3.9/4.0] 4.0
MPG	0.3	-	[0.4/0.4] 0.4	[0.5/0.6] 0.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 35

Ingredient	pphr
Epichlorohydrin Homopolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85
N330 Carbon Black	40

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.	
				mean	mean
R-22	8.7	8.7	5.6	[28.8/28.1]	28.5
R-32	3.7	3.4	3.3	[8.5/8.3]	8.4
R-124	0.5	1.0	1.8	[7.4/7.7]	7.6
R-134a	0.2	0.3	1.0	[2.7/3.0]	2.8
R-125	0.0	0.1	0.1	[0.9/0.9]	0.9
R-143a	0.2	0.4	0.6	[1.6/1.8]	1.7
R-152a	2.0	3.5	3.5	[8.5/8.4]	8.5
R-123	10.4	12.0	11.8	[45.7/45.8]	45.7
R-142b	1.1	2.8	2.9	[10.3/10.5]	10.4
R-134	0.4	1.5	2.8	[8.7/8.7]	8.8
AB	-0.1	-	[0.3/0.4]	0.4	[0.4/0.4]
MO	0.4	-	[1.1/1.0]	1.1	[2.0/1.9]
PEMA	5.8	-	[15.6/15.1]	15.4	[39.7/40.2]
PEBA	3.6	-	[4.7/5.0]	4.9	[12.4/12.5]
PPGD	4.1	-	[10.5/10.5]	10.5	[26.2/27.0]
PPGBM	0.4	-	[1.4/1.4]	1.4	[2.8/2.6]
MPG	0.2	-	[0.2/0.2]	0.2	[0.5/0.5]

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 36

Ingredient

pphr

Epichlorohydrin Copolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	36.3	36.5	36.0		[133/120]	126.0
R-32	6.9	6.4	6.3		[20.7/20.4]	20.6
R-124	22.7	22.3	22.0		[83.2/82.2]	82.7
R-134a	3.8	3.6	3.7		[12.1/12.1]	12.1
R-125	2.2	3.0	3.1		[10.6/10.6]	10.6
R-143a	1.2	1.6	1.6		[4.8/4.8]	4.8
R-152a	4.8	4.8	5.0		[16.3/16.0]	16.2
R-123	67.3	67.2	68.0		[418/418]	418.0
R-142b	6.8	6.6	5.8		[20.8/20.6]	20.7
R-134	13.4	13.3	12.7		[51.4/50.1]	50.8
AB	0.2	-	[0.5/0.1]	0.3	[0.4/0.4]	0.4
MO	0.5	-	[1.0/0.9]	1.0	[2.3/2.3]	2.3
PEMA	6.6	-	[6.7/7.0]	6.9	[17.2/17.6]	17.4
PEBA	3.6	-	[4.7/5.0]	4.9	[12.4/12.5]	12.5
PPGD	10.4	-	[12.4/12.5]	12.5	[33.1/33.7]	33.4
PPGBM	0.8	-	[0.9/1.0]	1.0	[1.4/1.6]	1.5
MPG	-0.1	-	[-0.3/-0.3]	-0.3	[-0.7/-0.7]	-0.7

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 37

Ingredient	pphr
Epichlorohydrin Copolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85
N330 Carbon Black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	25.6	26.1	23.8		[89.6/83.8]	86.7
R-32	5.5	5.7	5.4		[14.7/14.6]	14.7
R-124	16.4	15.9	15.6		[55.0/52.4]	53.7
R-134a	2.7	2.5	2.7		[8.8/8.3]	8.5
R-125	1.5	2.1	2.4		[7.3/7.3]	7.3
R-143a	0.8	1.1	1.2		[3.4]	3.4
R-152a	5.7	5.2	2.0		[11.6/11.5]	11.6
R-123	43.1	44.6	43.2		[210/113]	211.0
R-142b	5.0	5.3	4.8		[14.9/15.0]	15.0
R-134	9.8	9.2	9.0		[35.2/34.5]	34.9
AB	-0.2	-	[0.1/0.2]	0.1	[0.2/0.2]	0.2
MO	0.5	-	[0.5/0.9]	0.7	[1.9/1.9]	1.9
PEMA	3.9	-	[5.1/5.0]	5.1	[11.5/11.7]	11.6
PEBA	2.1	-	[3.8/3.7]	3.8	[8.5/8.7]	8.6
PPGD	6.5	-	[8.5/8.2]	8.4	[20.8/21.0]	20.9
PPGBM	0.2	-	[0.7/0.5]	0.6	[1.1/1.5]	1.3
MPG	-0.4	-	[-0.2/-0.1]	-0.2	[-0.2/-0.2]	-0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #38

Ingredient	pphr
Epichlorohydrin Terpolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	39.8	39.0	38.4		[154/145]	149.0
R-32	7.5	7.4	7.3		[21.7/21.0]	21.4
R-124	26.2	26.1	25.6		[97.0/95.0]	96.0
R-134a	4.3	3.4	4.5		[14.4/14.5]	14.5
R-125	2.8	3.2	3.4		[12.2/12.0]	12.1
R-143a	1.7	1.7	1.5		[4.8/4.7]	4.8
R-152a	6.9	6.7	6.8		[18.0/17.9]	18.0
R-123	69.4	69.5	70.5		[447/449]	448.0
R-142b	8.0	7.4	7.4		[22.5/22.3]	22.4
R-134	14.9	15.0	14.3		[56.4/56.3]	56.4
AB	0.2	-	[-1.5/0.3]	-0.6	[0.8/0.7]	0.8
MO	0.1	-	[0.8/0.9]	0.9	[2.6/2.7]	2.7
PEMA	5.4	-	[8.1/7.6]	7.9	[18.9/19.0]	19.0
PEBA	4.0	-	[5.1/6.4]	5.8	[13.3/13.5]	13.4
PPGD	10.9	-	[13.9/13.5]	13.7	[37.0/37.1]	37.1
PPGBM	0.2	-	[1.3/1.1]	1.2	[2.7/2.9]	2.8
MPG	0.0	-	[-0.1/-0.2]	-0.2	[0.2/0.3]	0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 39

Ingredient	pphr
Epichlorohydrin Terpolymer	100
Stearic Acid	1
Nickel Dibutyldithiocarbamate	1
Red Lead	5
Ethylene Thiourea	1.85
IRB6	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	26.7	26.8	26.3		[102/96.0	99.0
R-32	5.1	5.5	5.4		[15.4/15.2]	15.3
R-124	17.6	17.7	17.4		[70.4/68.9]	69.7
R-134a	3.0	3.0	3.1		[10.2/10.3]	10.2
R-125	2.0	2.5	3.0		[9.0/8.6]	8.8
R-143a	1.0	-	-		-	
R-152a	5.1	4.7	4.8		[12.6/12.6]	12.6
R-123	42.3	43.2	41.8		[227/227]	227.0
R-142b	5.5	5.5	5.1		[16.4/16.1]	16.3
R-134	9.8	10.0	10.3		[39.3/38.8]	39.1
AB	0.2	-	[-2.0/0.3]	-0.9	[0.2/0.3]	0.3
MO	1.3	-	[-1.1/1.0]	-0.1	[2.1/2.0]	2.1
PEMA	4.0	-	[5.2/5.2]	5.2	[12.9/13.0]	13.0
PEBA	1.8	-	[3.7/3.8]	3.8	[9.3/9.2]	9.3
PPGD	7.8	-	[8.7/8.6]	8.7	[22.7/22.9]	22.8
PPGBM	-0.2	-	[1.3/1.2]	1.3	[1.9/2.3]	2.1
MPG	0.8	-	[0.8/0.2]	0.5	[0.3/0.3]	0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 40

Ingredient

pphr

Silicone elastomer
Peroxide100
1.5

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.		% Wgt. Chg.	
				mean		mean
R-22	64.0	64.4	64.3		[395/332]	364.0
R-32						
R-124	53.9	54.1	52.8		[338/315]	326.0
R-134a	6.5	6.2	5.9		[26.6/25.3]	26.0
R-125	8.4	8.5	8.4		[34.3/33.5]	33.9
R-143a	11.2	11.5	11.0		[25.5/21.3]	23.4
R-152a	21.3	21.0	19.4		[53.6/50.2]	51.9
R-123	74.6	74.2	73.5		[639/635]	637.0
R-142b	66.8	67.1	66.2		[363/318]	341.0
R-134						
AB	14.8	-	[14.4/18.4]	16.4	[58.4/58.9]	58.7
MO	10.1	-	[9.2/10.1]	8.7	[26.9/26.2]	26.6
PEMA	1.7	-	[1.6/1.2]	1.4	[4.7/0.8]	2.8
PEBA	2.5	-	[2.9/2.9]	2.9	[7.7/7.8]	7.8
PPGD	0.6	-	[-0.6/-0.2]	-0.4	[-0.5/0.1]	-0.2
PPGBM	0.7	-	[0.3/0.5]	0.4	[0.1/0.1]	0.1
MPG	1.5	-	[0.4/0.3]	0.1	[-0.1/-0.6]	-0.4

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 41

Ingredient

pphr

Dimethyl Silicone Rubber

100

Dicumyl Peroxide on Calcium Carbonate

1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	50.0	51.9	52.4		[222/199]	211.0
R-32	5.8	5.9	5.8		[15.4/12.2]	13.8
R-124	41.5	41.0	40.0		[210/190]	200.0
R-134a	6.1	18.3	6.0		[18.5/16.4]	17.5
R-125	7.2	7.6	7.2		[21.7/21.8]	21.7
R-143a	9.9	9.8	9.3		[21.0/19.1]	20.1
R-152a	17.3	17.1	17.0		[49.0/39.7]	44.3
R-123	60.4	60.9	59.9		[398/387]	393.0
R-142b	53.0	51.6	50.7		[247/216]	232.0
R-134	4.8	5.1	5.5		[18.5/17.6]	18.1
AB	15.9	-	[15.7/15.9]	15.8	[44.6/44.2]	44.4
MO	7.9	-	[7.1/7.4]	7.3	[19.5/19.4]	19.5
PEMA	1.5	-	[1.2/1.5]	1.4	[3.7/3.7]	3.7
PEBA	2.8	-	[2.5/2.3]	2.4	[7.3/7.2]	7.2
PPGD	0.6	-	[0.2/0.2]	0.2	[0.2/0.2]	0.2
PPGBM	0.4	-	[-0.1/0.1]	0.0	[0.7/0.6]	0.6
MPG	4.7	-	[-0.3/-0.4]	-0.4	[-0.2/-0.4]	-0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 42

Ingredient

pphr

Methylphenylvinyl Silicone Rubber
Dicumyl Peroxide on Calcium Carbonate

100
0.6

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	50.8	51.3	50.5		[218/210]	214.0
R-32	4.8	4.8	4.7		[9.8/8.8]	9.3
R-124	41.8	41.8	42.6		[195/193]	194.0
R-134a	5.1	5.3	5.4		[17.0/17.1]	17.1
R-125	5.8	5.9	6.0		[16.0/17.0]	16.6
R-143a	6.8	6.8	6.1		[14.5/12.9]	13.7
R-152a	14.0	14.6	14.8		[37.7/33.1]	35.4
R-123	62.8	63.2	65.1		[415/399]	407.0
R-142b	52.8	55.6	53.5		[252/227]	240.0
R-134	4.7	4.4	5.9		[14.7/13.3]	14.0
AB	25.9	-	[26.5/26.7]	26.6	[78.1/77.4]	77.8
MO	11.5	-	[12.0/12.5]	12.3	[32.5/32.8]	32.7
PEMA	9.7	-	[9.6/8.0]	8.8	[26.3/26.2]	26.2
PEBA	12.1	-	[12.3/12.9]	12.6	[37.2/37.2]	37.2
PPGD	2.6	-	[1.6/0.6]	1.1	[3.7/3.8]	3.7
PPGBM	4.5	-	[4.2/3.5]	3.8	[9.5/9.5]	9.5
MPG	3.0	-	[2.8/2.8]	2.8	[8.6/8.9]	8.8

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 43

Ingredient

pphr

Silicone Rubber

100

Dicumyl Peroxide on Calcium Carbonate

0.8

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	mean	% Wgt. Chg. mean
R-22	21.3	21.6	22.1	[97.1/86.6]	91.9
R-32	3.4	3.8	3.7	[8.7/7.2]	8.0
R-124	17.5	17.2	17.4	[89.2/82.3]	85.7
R-134a	3.6	3.9	3.6	[12.6/12.0]	12.3
R-125	4.5	4.4	4.8	[15.8/15.5]	15.7
R-143a	6.1	5.9	5.9	[15.7/13.8]	14.8
R-152a	9.1	9.1	9.2	[28.0/25.7]	26.9
R-123	23.0	23.0	22.3	[139/136]	137.0
R-142b	22.0	22.0	22.0	[91.5]	91.5
R-134	3.2	3.0	3.3	[12.8/12.1]	12.5
AB	8.5	-	[8.1/7.9]	8.0	[22.1/22.0]
MO	5.4	-	[4.5/4.6]	4.6	[12.6/12.5]
PEMA	2.2	-	[1.7/1.8]	1.8	[5.1/5.0]
PEBA	2.7	-	[2.3/2.1]	2.2	[7.0/7.0]
PPGD	0.5	-	[0.4/0.5]	0.4	[1.6/1.4]
PPGBM	0.8	-	[0.6/0.9]	0.7	[2.7/2.6]
MPG	0.9	-	[0.7/0.5]	0.6	[2.5/2.7]

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 44

Ingredient	pphr
Fluorosilicone	100
Iron Oxide	1.5
Bis(2,4-dichlorobenzoyl peroxide)	1.3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	42.0	42.0	43.0		[141/129]	135.0
R-32	31.6	31.7	31.4		[68.0/63.6]	65.8
R-124	32.5	33.1	32.2		[137/127]	132.0
R-134a	34.6	35.0	35.4		[127/122]	125.0
R-125	15.0	15.0	15.0		[50.0/48.2]	49.0
R-143a	24.0	24.0	24.5		[64.1/58.0]	61.0
R-152a	39.6	39.8	39.4		[106/102]	104.0
R-123	31.7	31.0	31.4		[137/137]	137.0
R-142b	43.3	43.0	42.0		[151]	151.0
R-134	34.0	36.2	33.3		[145/134]	140.0
AB	0.8	-	[-0.3/0.3]	0.0	[1.1/1.0]	1.1
MO	1.0	-	[0.6/0.4]	0.5	[0.8/0.9]	0.9
PEMA	2.5	-	[2.1/1.9]	2.0	[4.9/4.9]	4.9
PEBA	2.3	-	[2.7/3.6]	3.1	[7.5/7.5]	7.5
PPGD	1.1	-	[0.7/0.7]	0.7	[1.3/1.4]	1.3
PPGBM	0	-	[-0.1/0.1]	0.0	[0.6/0.5]	0.6
MPG	-0.6	-	[-0.7/0.0]	-0.3	[0.3/0.5]	0.4

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 45

Ingredient

pphr

EPDM/Polypropylene TPE Shore A 87

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day		
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.	% Wgt. Chg.	
			mean		mean	
R-22	-0.7	-0.9	-0.9	[5.9/3.1]	4.5	
R-32	0.7	0.9	0.8	[3.3/3.2]	3.3	
R-124	-0.8	-0.9	-1.3	[8.8/8.9]	8.9	
R-134a	0.0		0.1	[2.4/2.4]	2.4	
R-125	1.0	1.4	1.7	[9.6/10.4]	10.0	
R-143a	0.8	0.6	0.9	[2.9/3.0]	2.9	
R-152a	0.8	0.7	0.8	[5.9/4.2]	5.1	
R-123	0.3	0.1	0.1	[19.2/19.2]	19.2	
R-142b	-0.1	-0.3	-0.6	[7.0/6.2]	6.6	
R-134	0.4	0.5	0.5	[2.7/2.5]	2.6	
AB	3.6	-	[4.5/4.6]	4.6	[17.3/18.1]	17.7
MO	6.6	-	[6.6/6.7]	6.7	[26.0/26.2]	26.1
PEMA	-1.3	-	[-1.7/-1.7]	-1.7	[-1.7/-2.0]	-1.9
PEBA	-0.8	-	[-1.2/-1.6]	-1.4	[-1.7/-1.8]	-1.8
PPGD	-2.8	-	[-3.5/-2.7]	-3.1	[-9.0/-8.9]	-8.9
PPGBM	-1.2	-	[-1.9/-2.4]	-2.2	[-4.4/-4.4]	-4.4
MPG	-1.7	-	[-2.1/-2.5]	-2.3	[-4.1/-3.7]	-3.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 46

Ingredient

pphr

EPDM/Polypropylene TPE Shore A 73

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	-2.5	-3.2	-3.5		[-7.0/-8.1]	-7.6
R-32	0.7	0.7	0.7		[3.6/3.5]	3.6
R-124	-2.4	-3.4	-4.2		[-5.9/-6.4]	-6.2
R-134a	0.4		0.1		[2.6/2.7]	2.6
R-125	1.3	2.7	3.2		[11.3/12.9]	12.1
R-143a	0.1	0.2	0.4		[3.3/3.5]	3.4
R-152a	0.7	0.3	0.6		[4.5/3.9]	4.2
R-123	-1.3	-1.3	-1.4		[15.2/15.1]	15.2
R-142b	-3.3	-3.8	-4.2		[-6.1/-6.4]	-6.3
R-134	0.6	0.6	0.5		[2.7/2.9]	2.8
AB	8.7		[11.1/10.3]	10.7	[38.6/38.5]	38.6
MO	13.8		[13.2/14.1]	13.7	[54.2/54.0]	54.1
PEMA	-3.9		[-8.0/-5.1]	-6.6	[-13.5/-13.7]	-13.6
PEBA	-3.2		[-4.2/-4.2]	-4.2	[-12.5/-12.6]	-12.6
PPGD	-5.6		[-6.0/-7.3]	-6.7	[-21.6/-21.3]	-21.5
PPGBM	-4.0		[-6.1/-6.5]	-6.3	[-18.1/-17.9]	-18.0
MPG	-5.0		[-6.4/-6.4]	-6.4	[-18.6/-18.6]	-18.6

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula # 47

Ingredient

pphr

EPDM/Polypropylene TPE Shore D 40

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	-0.4	-0.4	-0.5		[7.6/3.4]	5.5
R-32	0.4	0.2	0.2		[3.0/2.7]	2.9
R-124	-0.4	-0.5	-0.5		[11.8/10.6]	11.2
R-134a	0.2		0.3		[2.2/2.1]	2.1
R-125	0.8	1.7	1.8		[9.4/9.5]	9.4
R-143a	0.7	0.6	0.6		[2.8/2.7]	2.7
R-152a	0.3	0.6	0.6		[6.1/4.8]	5.4
R-123	0.9	0.5	0.5		[18.8/18.5]	18.7
R-142b	0.2	-0.2	-0.2		[8.1/7.0]	7.6
R-134	0.1	0.2	0.1		[1.5/1.8]	1.7
AB	2.9	-	[3.4/2.9]	3.2	[13.5/14.4]	14.0
MO			[4.1/3.9]	4.0	[18.3/18.0]	18.2
PEMA	-0.5	-	[-0.6/-0.2]	-0.4	[1.0/1.2]	1.1
PEBA	-0.5	-	[0.1/-0.4]	-0.2	[0.9/1.1]	1.0
PPGD	-1.0	-	[-1.2/-1.1]	-1.2	[-3.2/-3.2]	-3.2
PPGBM	-0.4	-	[-0.3/-0.9]	-0.5	[-0.4/-0.5]	-0.5
MPG	-0.2	-	[0.4/-0.7]	-0.2	[-0.3/-0.3]	-0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 43

Ingredient

pphr

EPDM/Polypropylene TPE Shore D 50

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	mean	% Wgt. Chg. mean
R-22	0.1	0.5	0.1		[7.6/6.4] 7.0
R-32					
R-124	0.1	-0.2	-0.3		[9.7/9.3] 9.5
R-134a	0.3		0.3		[1.9/2.2] 2.1
R-125	0.6	1.3	1.4		[8.8/9.4] 9.1
R-143a	0.2	0.4	0.7		[2.3/2.4] 2.3
R-152a	0.1	-0.2	-0.1		[2.0/1.2] 1.6
R-123	1.4	1.0	1.1		[17.8/17.8] 17.8
R-142b	0.7	0.7	0.4		[7.9/7.7] 7.8
R-134	0.1	0.2	-0.1		[2.6/1.8] 2.2
AB	1.5	-	[2.5/2.2] 2.4		[9.5/9.2] 9.4
MO	2.6	-	[2.7/2.6] 2.7		[13.9/13.7] 13.8
PEMA	0.6	-	[0.2/0.0] 0.1		[2.0/1.6] 1.8
PEBA	0.0	-	[-2.5/0.0] -1.3		[1.5/1.8] 1.7
PPGD	-0.6	-	[-1.1/-1.3] -1.2		[-1.5/-1.6] -1.6
PPGBM	-0.5	-	[-0.4/-0.4] -0.4		[0.8/0.7] 0.8
MPG	-0.2	-	[-0.8/-0.7] -0.8		[0.9/0.8] 0.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 49

Ingredient

pphr

Nitrile/Polypropylene TPE Shore A 87

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.		% Wgt. Chg.	
				mean		mean
R-22	9.9	10.3	10.2		[65.2/54.7]	60.0
R-32						
R-124	5.7	5.8	6.6		[51.1/50.0]	50.6
R-134a	0.4	0.7	-0.2		[4.4/4.0]	4.2
R-125	1.3	14.2	1.7		[7.8/8.8]	8.3
R-143a	1.1	0.4	-0.4		[0.7/1.5]	1.1
R-152a	1.0	0.3	0.4		[2.6/3.4]	3.0
R-123	19.6	20.0	20.6		[140/139]	139.0
R-142b	2.3	1.7	1.7		[12.3/12.1]	12.2
R-134	2.1	1.7	1.2		[14.7/14.6]	14.7
AB	1.0	-	[0.5/0.7]	0.6	[-0.9/-0.9]	-0.9
MO	1.8	-	[0.9/0.4]	0.7	[1.1/1.1]	1.1
PEMA	0.9	-	[0.7/1.1]	0.9	[3.6/3.6]	3.6
PEBA	0.0	-	[0.3/0.9]	0.6	[2.5/2.5]	2.5
PPGD	0.6	-	[0.4/-0.1]	0.2	[0.5/0.8]	0.6
PPGBM	-0.2	-	[-0.4/-0.8]	-0.6	[-2.2/-2.1]	-2.1
MPG	-1.4	-	[-1.2/1.2]	1.2	[-2.7/-2.4]	-2.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 50

Ingredient

pphr

Nitrile/Polypropylene TPE Shore A 80

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	14.3	14.6	14.6		[78.4/75.5]	77.0
R-32						
R-124	10.5	10.2	10.6		[77.7/74.8]	76.3
R-134a	0.7	-0.2	-1.3		[1.2/3.7]	2.5
R-125	1.8	1.7	0.3		[4.8/4.7]	4.7
R-143a	0.4	2.8	-1.2		[-2.6/-0.2]	-1.4
R-152a	-0.4	-0.3	-0.4		[0.4/0.1]	0.3
R-123	31.1	31.5	31.8		[216/216]	216.0
R-142b	1.5	1.1	0.6		[11.1/11.5]	11.3
R-134	3.0	2.2	1.6		[19.1/19.4]	19.3
AB	-0.3	-	[-1.4/-1.3]	-1.4	[-5.9/-5.7]	-5.8
MO	0.7	-	[-0.8/-0.9]	-0.9	[-3.3/-3.1]	-3.2
PEMA	1.4	-	[0.9/0.8]	0.9	[3.3/3.5]	3.4
PEBA	0.4	-	[0.3/-0.1]	0.1	[1.4/1.4]	1.4
PPGD	1.0	-	[0.6/0.7]	0.6	[1.3/1.5]	1.4
PPGBM	-0.8	-	[-1.9/-1.9]	-1.9	[-6.0/-6.2]	-6.1
MPG	-1.9	-	[-2.8/-2.5]	-2.7	[-7.7/-7.9]	-7.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 51

Ingredient

pphr

Nitrile/Polypropylene TPE Shore D 40

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	mean	% Wgt. Chg. mean
R-22	6.9	7.1	7.4	[47.4/42.9]	45.2
R-32					
R-124	4.7	4.6	4.5	[39.7/39.0]	39.4
R-134a	0.9	0.9	0.5	[6.6/7.2]	6.9
R-125	1.0	1.8	1.8	[7.5/8.2]	7.9
R-143a	0.8	1.3	0.3	[1.8/2.0]	1.4
R-152a	1.2	0.4	0.3	[3.0/3.0]	3.0
R-123	14.2	14.5	15.4	[103/101]	102.0
R-142b	2.3	1.9	1.7	[12.0/11.5]	11.8
R-134	1.6	1.6	0.8	[11.9/12.6]	12.3
AB	1.4	-	[0.7/1.1]	0.9	[1.0/1.0]
MO	1.8	-	[1.1/1.1]	1.1	[2.9/3.1]
PEMA	0.8	-	[0.9/0.8]	0.8	[3.4/3.3]
PEBA	0	-	[0.5/0.4]	0.5	[2.8/2.6]
PPGD	0	-	[-0.2/-0.2]	-0.2	[0.4/0.5]
PPGBM	-0.1	-	[-0.2/-0.4]	-0.3	[-0.8/-0.9]
MPG	-0.6	-	[-1.0/-0.6]	-0.8	[-1.6/-1.5]

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 52

Ingredient

pphr

Polyester TPE (40 shore D)

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	mean	mean
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.		
R-22	25.5	25.7	26.4	[128/124]		126.0
R-32						
R-124	19.9	19.8	19.3	[109/102]		105.0
R-134a	3.7	3.3	3.3	[12.3/12.0]		12.2
R-125	4.4	4.6	4.9	[16.4/16.2]		16.3
R-143a	1.6	2.2	2.1	[5.3/5.2]		5.3
R-152a	4.1	4.4	4.2	[12.1/11.5]		11.8
R-123						
R-142b	7.1	6.6	6.7	[24.4/22.8]		23.6
R-134						
AB	2.4	-	[2.8/3.3]	3.1	[6.4/6.3]	6.4
MO	1.8	-	[9.5/8.4]	6.5	[8.7/8.9]	8.8
PEMA	3.2	-	[4.6/4.7]	4.7	[12.7/12.9]	12.8
PEBA	3.0	-	[4.7/4.4]	4.6	[10.3/10.5]	10.4
PPGD	3.5	-	[4.2/4.4]	4.3	[11.4/11.4]	11.4
PPGBM	1.6	-	[2.3/2.7]	2.5	[6.0/6.2]	6.1
MPG	0.7	-	[1.9/1.9]	1.9	[3.8/3.6]	3.7

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 53

Ingredient

pphr

Polyester TPE (63 shore D)

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	14.4	14.0	13.8	[52.0/47.6] 49.8
R-32				
R-124	8.6	9.5	9.4	[39.0/38.3] 38.7
R-134a	2.4	2.7	2.5	[8.7/8.3] 8.5
R-125	1.9	2.6	2.8	[10.0/10.4] 10.2
R-143a	1.4	1.3	1.2	[3.5/3.4] 3.5
R-152a	3.5	3.0	2.8	[1.1/1.4] 1.2
R-123	25.4	25.0	24.9	[125/128] 126.0
R-142b	5.0	4.4	4.5	[13.9/13.6] 13.7
R-134				
AB	0.8		[1.3/1.7] 1.5	[2.7/3.1] 2.9
MO	0.9	-	[1.9/2.0] 2.0	[4.6/4.7] 4.7
PEMA	0.6	-	[1.9/1.8] 1.9	[5.2/5.4] 5.3
PEBA	0.8	-	[1.8/1.6] 1.7	[4.0/4.2] 4.1
PPGD	1.2	-	[1.9/2.0] 2.0	[5.1/4.8] 5.0
PPGBM	0.6	-	[0.8/0.9] 0.9	[2.5/2.4] 2.5
MPG	0.3	-	[0.6/0.5] 0.6	[1.4/1.5] 1.5

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 54

Ingredient

pphr

Polyester TPE (72 shore D)

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	9.9	10.3	9.9		[40.7/38.6]	39.7
R-32						
R-124	7.2	7.0	6.9		[2.9/2.4]	2.7
R-134a	1.2	1.9	2.0		[7.7/7.5]	7.6
R-125	0.4	2.1	2.2		[7.4/7.8]	7.6
R-143a	1.1	1.4	1.2		[2.9/2.8]	2.9
R-152a	3.1	2.6	2.6		[6.8/6.5]	6.7
R-123	14.7	15.4	16.4		[74.4/80.5]	77.5
R-142b	3.3	3.6	3.4		[12.9/11.2]	12.1
R-134						
AB	0.3	-	[0.7/1.0]	0.9	[2.0/2.1]	2.1
MO	0.7	-	[1.0/1.9]	1.5	[3.4/3.2]	3.3
PEMA	0.0	-	[1.2/1.2]	1.2	[3.4/3.6]	3.5
PEBA	0.0	-	[0.8/1.1]	1.0	[2.8/2.7]	2.8
PPGD	0.6	-	[1.4/1.0]	1.2	[3.5/3.6]	3.6
PPGBM	0.3	-	[0.5/0.6]	0.6	[1.8/1.6]	1.7
MPG	-0.3	-	[-0.1/0.5]	0.2	[0.9/1.0]	1.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 55

Ingredient

pphr

Polyester TPE (55 shore D)

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	7.0	6.8	6.9		[26.8/25.3]	26.1
R-32						
R-124	0.8	4.2	4.2		[16.9/17.1]	17.0
R-134a	0.2	0.8	1.3		[3.8/3.8]	3.8
R-125	-0.1	0.1	0.3		[2.5/2.1]	2.3
R-143a	0.1	0.2	0.4		[0.8/0.8]	0.8
R-152a	1.0	2.1	1.9		[5.5/5.3]	5.4
R-123	6.1	9.6	9.5		[40.4/42.1]	41.3
R-142b	0.2	1.8	2.2		[7.6/7.6]	7.6
R-134						
AB	-0.2		[0.1/-0.1]	0.0	[0.3/0.4]	0.4
MO	0.2		[0.4/0.3]	0.4	[0.7/0.9]	0.8
PEMA	-0.1		[-0.1/-0.2]	-0.1	[0.6/0.4]	0.5
PEBA	0.2		[0.1/0.3]	0.2	[0.1/0.2]	0.2
PPGD	-0.4		[-0.3/-0.6]	-0.5	[1.0/1.1]	1.1
PPGBM	0.1		[-0.1/-0.1]	-0.1	[0.2/0.2]	0.2
MPG	-0.1		[-0.1/-0.1]	-0.1	[0.1/0.1]	0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 56

Ingredient	pphr
FA Polysulfide Rubber	100
Zinc oxide	10
Stearic acid	0.5
2,2'-Benzothiazyl disulfide	0.4
Diphenyl guanidine	0.1
2-mercapto imidazoline	0.1

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg. mean	% Wg. Chg. mean
R-22	3.5	4.4	3.8	[12.3/12.3] 12.3
R-32				
R-124	-0.1	0.4	0.5	[1.6/1.7] 1.7
R-134a	-0.7	-0.5	-0.4	[-0.4/0.4] 0.0
R-125	-0.1	0.3	0.6	[0.5/1.0] 0.8
R-143a	-0.2	0.3	0.1	[-0.3/0.1] -0.1
R-152a	0.5	1.0	0.5	[1.0/1.5] 1.3
R-123	7.6	8.0	7.8	[32.2/32.3] 32.2
R-142b	0.5	0.7	1.0	[2.3/2.7] 2.5
R-134				
AB	-0.3	-	[-0.8/-0.9] -0.9	[-3.9/-3.7] -3.8
MO	0.4	-	[-0.4/-0.2] -0.3	[-1.8/-1.1] -1.5
PEMA	-0.3	-	[-3.0/-2.7] -2.9	[-9.0/-8.3] -8.7
PEBA	-0.6	-	[-3.9/-3.1] -3.5	[-10.8/-8.7] -9.8
PPGD	0.0	-	[-3.7/-2.4] -3.1	[-11.2/-10.4] -10.8
PPGBM	-1.9	-	[-3.2/-4.1] -3.7	[-8.6/-6.5] -7.6
MPG	-1.1	-	[-2.6/-2.5] -2.6	[-8.4/-6.2] -7.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 57

Ingredient	pphr
FA Polysulfide Rubber	100
Zinc oxide	10
Stearic acid	0.5
2,2'-Benzothiazyl disulfide	0.4
Diphenyl guanidine	0.1
2-mercapto imidazoline	0.1
IRB6 (Carbon black)	60

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	4.0	2.3	3.1		[8.1/8.3]	8.2
R-32						
R-124	0.1	0.2	0.3		[0.9/1.2]	1.1
R-134a	-0.1	-0.1	0.1		[-0.3/-0.1]	-0.2
R-125						
R-143a	-0.4	0.3	-0.1		[-0.3/-0.2]	-0.3
R-152a	0.7	1.0	0.9		[0.6/0.8]	0.7
R-123	4.1	5.9	6.0		[20.3/20.5]	20.4
R-142b	0.2	0	0.5		[1.6/1.9]	1.8
R-134						
AB	-0.5	-	[-0.9/-0.7]	-0.8	[-1.7/-1.7]	-1.7
MO	-0.1	-	[-0.5/-0.7]	-0.6	[-0.4/-0.2]	-0.3
PEM0	-0.5	-	[-0.6/-1.4]	-1.0	[-1.5/-1.6]	-1.6
PEBA	-0.7	-	[-0.7/-0.8]	-0.8	[-1.5/-1.7]	-1.6
PPGD	-0.6	-	[-0.6/-0.5]	-0.6	[-1.7/-1.4]	-1.6
PPGBM	-0.8	-	[-1.0/-0.7]	-0.8	[-1.9/-1.3]	-1.6
MPG	-0.8	-	[-0.6/-0.7]	-0.7	[-2.4/-2.2]	-2.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 58

Ingredient

pphr

ST Polysulfide Rubber

100

Zinc peroxide

5

Stearic acid

1

Calcium Hydroxide

1

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	8.1	10.6	8.6		[30.6/30.2]	30.4
R-32						
R-124	1.2	1.7	2.5		[11.2/9.6]	10.4
R-134a	-0.1	-0.1	-0.1		[1.5/2.0]	1.8
R-125	-1.2	-0.1	0.2		[1.8/2.4]	2.1
R-143a	0.1	0.2	0.3		[08/0.9]	0.9
R-152a	2.1	2.3	1.6		[3.7/4.0]	3.9
R-123	59.1	57.6	56.0		[330/321]	325.0
R-142b	1.3	2.3	2.1		[6.5/7.1]	6.8
R-134						
AB		-				
MO	-0.1	-	[-1.8/-1.3]	-1.6	[-4.5/-2.8]	-3.7
PEMA	1.0	-	[-3.9/-3.7]	-3.8	[-11.0/-10.5]	-10.8
PEBA		-				
PPGD		-				
PPGBM	-0.7	-	[-4.8/-4.8]	-4.8	[-12.3/-10.7]	-11.5
MPG		-				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 59

Ingredient	pphr
ST Polysulfide Rubber	100
Zinc peroxide	5
Stearic acid	1
Calcium Hydroxide	1
IRB6 (Carbon black)	60

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	39.6	7.8	6.3		[0.9/0.1]	0.5
R-32						
R-124	1.3	2.2	1.4		[5.1/5.4]	5.3
R-134a	0.6	-0.1	0.1		[0.9/1.1]	1.0
R-125	-4.1	0.9	0.7		[0.9/1.8]	1.4
R-143a	0.2	0.3	0.3		[0.3/0.3]	0.3
R-152a	1.6	1.9	1.5		[2.1/2.2]	2.2
R-123	26.9	26.5	27.2		[115/116]	116.0
R-142b	0.8	1.7	1.6		[3.4/3.3]	3.4
R-134						
AB	-0.4	-	[-0.9/-0.9]	-0.9	[-2.0/-2.3]	-2.2
MO	0.2	-	[-0.5/-0.4]	-0.5	[-0.9/-0.5]	-0.7
PEMA	-0.3	-	[-1.7/-1.4]	-1.6	[-3.4/-2.8]	-3.1
PEBA	-0.4	-	[-1.7/-2.0]	-1.9	[-3.4/-4.0]	-3.7
PPGD	0.6	-	[-0.5/-0.7]	-0.6	[-2.0/-1.3]	-1.7
PPGBM	-0.5	-	[-2.0/-2.3]	-2.2	[-4.0/-2.4]	-3.2
MPG	-3.4	-	[-2.2/-1.7]	-2.0	[-.34/-3.1]	-3.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 60

Ingredient

pphr

Polyurethane (Ether - 80 shore A)

100

Moca - 95% stoichiometry

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	31.0	31.0	31.3		[151/144]	148.0
R-32						
R-124	29.6	29.6	29.7		[157/158]	158.0
R-134a	4.6	4.6	5.0		[20.9/20.8]	20.9
R-125	7.0	6.9	6.9		[27.3/27.4]	27.4
R-143a	2.8	2.8	2.6		[9.6/9.6]	9.6
R-152a	6.3	6.6	6.5		[1.7/1.9]	1.8
R-123	57.7	56.4	58.7		[419/424]	422.0
R-142b	12.1	12.1	12.1		[47.4/46.6]	47.0
R-134						
AB	2.8	-	[5.1/5.0]	5.1	[14.4/14.1]	14.3
MO	4.8	-	[6.0/5.5]	5.8	[16.8/16.5]	16.7
PEMA	3.5	-	[7.2/7.1]	7.2	[23.2/23.1]	23.2
PEBA	2.3	-	[5.5/4.8]	5.2	[19.8/19.5]	19.7
PPGD	7.4	-	[13.6/13.5]	13.6	[41.0/41.0]	41.0
PPGBM	2.8	-	[6.0/5.8]	5.9	[19.5/19.3]	19.4
MPG	1.5	-	[3.0/6.2]	4.6	[11.1/11.3]	11.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 61

Ingredient

pphr

Polyurethane (Ether - 50 shore D)

100

Moca - 95% stoichiometry

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	15.5	15.7	16.1		[58.3/79.2]	6.8
R-32						
R-124	11.5	12.7	13.0		[59.9/58.1]	59.0
R-134a	1.0	2.0	2.0		[10.1/8.9]	9.5
R-125	0.1	2.1	1.9		[8.5/8.4]	8.5
R-143a	0.6	1.2	1.3		[4.2/4.2]	4.2
R-152a	2.9	3.3	2.5		[10.0/10.0]	10.0
R-123	28.9	29.0	30.6		[168/173]	170.0
R-142b	2.8	5.9	5.1		[19.4/19.2]	19.3
R-134						
AB	-0.3	-	[0.4/1.2]	0.8	[2.0/1.8]	1.9
MO	0.1	-	[1.8/1.4]	1.6	[2.9/3.9]	3.4
PEMA	0.2	-	[2.0/0.8]	1.4	[2.5/2.9]	2.7
PEBA	0.5	-	[0.9/0.9]	0.9	[2.2/2.6]	2.4
PPGD	0.7	-	[3.8/4.5]	4.2	[12.4/13.9]	13.2
PPGBM	0.2	-	[1.0/1.3]	1.2	[2.6/2.9]	2.8
MPG	-0.4	-	[0.3/0.1]	0.2	[1.2/0.9]	1.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 62

Ingredient

pphr

Polyurethane (Ester - 80 shore A)
Moca - 95% stoichiometry

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	32.2	32.1	32.1		[135/144]	13.0
R-32						
R-124	32.2	31.7	32.5		[211/147]	179.0
R-134a	2.2	3.8	3.7		[14.0/14.3]	14.2
R-125	0.7	1.3	2.4		[10.9/10.7]	10.8
R-143a	0.2	0.9	1.0		[4.5/4.7]	4.6
R-152a	4.4	4.8	4.3		[-9.9/16.3]	3.2
R-123	61.4	61.8	62.0		[391/374]	382.0
R-142b	2.7	4.4	5.0		[16.3/16.8]	16.6
R-134	17.5	20.7	19.2		[88.0/84.8]	86.4
AB	0.5	-	[11.85/-0.5]	5.5	[0.4/0.3]	0.4
MO	0.4	-	[0.1/-0.1]	0.0	[3.1/1.2]	2.2
PEMA	-0.4	-	[-0.2/0.8]	0.3	[1.2/1.4]	1.3
PEBA	0.3	-	[0.2/0.5]	0.4	[1.1/1.4]	1.3
PPGD	1.2	-	[5.4/4.6]	5.0	[14.6/12.7]	13.7
PPGBM	-1.1	-	[-1.1/-0.1]	-0.6	[1.0/0.6]	0.8
MPG	0.8	-	[0.1/-0.6]	0.3	[8.2/-7.6]	0.3

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Polyglycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 63

Ingredient

pphr

Polyurethane (Ether - 50 shore D)

100

Moca - 95% stoichiometry

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	17.0	15.7	16.5		[59.7/58.2]	59.0
R-32						
R-124	2.8	8.9	8.7		[39.6/39.6]	39.6
R-134a	1.1	1.0	1.4		[5.0/5.8]	5.4
R-125	-2.0	-0.9	0.8		[2.3/2.4]	2.4
R-143a	2.4	0.3	0.5		[1.1/1.2]	1.2
R-152a	0.2	3.0	3.3		[8.8/8.9]	8.9
R-123	20.0	24.0	24.0		[115/114]	115.0
R-142b	0.1	1.3	1.5		[6.7/7.2]	6.9
R-134						
AB	0.1	-	[0.6/-0.7]	-0.1	[-0.4/-0.3]	-0.4
MO		-				
PEM0	-2.4	-	[-2.1/-1.5]	-1.8	[-0.1/-0.1]	-0.1
PEBA	-2.0	-	[0.3/0.2]	0.3	[-0.1/-0.1]	-0.1
PPGD	0.1	-	[1.3/1.0]	1.2	[2.6/2.5]	2.6
PPGBM		-				
MPG	-0.3	-	[-0.4/-1.1]	-0.8	[-0.3/-0.3]	-0.3

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 64

Ingredient

pphr

Polyurethane (Millable - Ester based)

100

Moca - 95% stoichiometry

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg. mean	% Wgt. Chg. mean
R-22	48.4	46.0	48.7	[196/152] 174.0
R-32				
R-124	49.3	48.7	51.9	[299/270] 285.0
R-134a	4.6	4.0	4.0	[15.9/14.9] 15.4
R-125	1.5	3.0	2.6	[11.8/12.2] 12.0
R-143a	0.2	1.4	1.3	[3.3/3.5] 3.4
R-152a	5.8	5.8	6.0	[15.1/14.8] 15.0
R-123	92.9	92.4	93.6	[717/752] 734.0
R-142b	6.4	5.0	4.7	[16.4/16.4] 16.4
R-134				
AB				
MO				
PEMA				
PEBA				
PPGD				
PPGBM				
MPG				

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 65

Ingredient

pphr

Polyurethane (Millable Ether based)
Moca - 95% stoichiometry

100

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.	
				mean	mean
R-22	48.0	48.0	46.9	[246/235]	240.0
R-32					
R-124	52.7	52.9	51.4	[343/325]	334.0
R-134a	5.4	5.6	5.3	[19.9/19.9]	19.9
R-125	7.2	7.0	6.8	[26.4/26.9]	26.7
R-143a	2.8	2.7	2.7	[9.2/9.3]	9.3
R-152a	7.2	6.7	6.9	[21.3/21.6]	21.5
R-123	96.2	98.8	103	[917/920]	918.0
R-142b	15.5	15.8	15.2	[61.2/59.4]	60.3
R-134					
AB	6.6	-	[9.7/9.8] 9.8	[24.7/25.2]	25.0
MO	9.0	-	[7.8/8.7] 8.3	[26.0/27.0]	26.5
PEMA	22.9	-	[27.3/27.4] 27.4	[100/98.9]	99.6
PEBA	8.9	-	[17.5/18.7] 18.1	[60.8/58.9]	59.9
PPGD	23.5	-	[48.2/48.5] 48.4	[216/216]	216.0
PPGBM	22.7	-	[32.8/31.0] 31.9	[126/121]	123.0
MPG	4.3	-	[11.1/10.6] 10.9	[36.0/36.0]	36.0

PEMA - Pentaerythritol Ester Mixed Acid
PEBA - Pentaerythritol Ester Branched Acid
PPGBM - Polypropylene Glycol Butyl Monoether
MO - Mineral Oil

MPG - Modified Poly glycol
PPGD - Polypropylene Glycol Diol
AB - Alkyl Benzene

Formula # 68

Ingredient

pphr

Chlorosulfonated polyethylene	100
Litharge	25
Benzothiazyl disulfide	0.5
Sulfur	2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	mean	14 Day % Wgt. Chg.	mean
R-22	9.1	8.6	8.2		[27.8/27.9]	27.8
R-32						
R-124	1.1	1.4	3.5		[12.7/12.8]	12.8
R-134a	0.3	0.3	1.2		[3.5/3.2]	3.3
R-125	0.7	0.9	1.2		[3.5/2.8]	3.2
R-143a	1.0	1.4	2.2		[5.0/4.9]	4.9
R-152a	1.8	3.0	3.5		[8.3/8.4]	8.4
R-123	18.6	18.9	18.8		[75.2/75.0]	75.1
R-142b	3.6	6.0	6.1		[17.7/17.9]	17.8
R-134	0.5	0.9	1.5		[4.7/4.8]	4.8
AB	3.2	-	[7.6/7.3]	7.5	[15.5/15.5]	15.5
MO	4.3	-	[12.2/12.1]	12.2	[29.0/28.5]	28.8
PEMA	10.0	-	[23.2/23.0]	23.1	[64.0/64.0]	64.0
PEBA	-0.6	-	[15.5/15.3]	15.4	[40.0/39.0]	39.5
PPGD	1.7	-	[3.5/3.2]	3.4	[7.5/7.3]	7.4
PPGBM	0.3	-	[1.5/1.7]	1.6	[3.7/3.7]	3.7
MPG	0.0	-	[0.3/0.2]	0.3	[1.1/1.1]	1.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGFM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 69

Ingredient	pphr
Chlorosulfonated polyethylene (Cl 35%, S 1.0%)	100
Magnesia	4
Pentaerythritol	3
Dipentamethylenethiuram hexasulfide	2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day	
			% Dia. Chg. mean		% Wgt. Chg. mean	
R-22	7.9	7.5	7.5		[30.5/30.9]	30.7
R-32						
R-124	1.0	2.7	3.0		[13.0/13.1]	13.1
R-134a	0.3	0.6	1.0		[3.8/3.1]	3.5
R-125	0.7	1.6	1.9		[5.7/5.7]	5.7
R-143a	0.3	0.9	1.1		[3.0/2.5]	2.8
R-152a	1.7	3.0	3.0		[8.4/8.4]	8.4
R-123	19.2	18.6	18.1		[87.0/89.1]	88.0
R-142b	4.6	5.8	5.8		[19.7/19.9]	19.8
R-134						
AB	2.4	-	[8.2/5.2]	6.7	[18.7/14.3]	16.5
MO		-				
PEMA		-				
PEBA	5.5	-	[22.7/24.3]	23.5	[72.7/76.8]	74.8
PPGD	-0.4	-	[1.8/1.7]	1.3	[5.1/3.8]	4.5
PPGBM		-				
MPG	-1.0	-	[0.2/0.1]	0.2	[1.0/1.2]	1.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 67

Ingredient	pphr
Chlorosulfonated polyethylene (Cl 29%, S 1.4%)	100
Litharge	25
2,2'-Benzothiazyl disulfide	0.5
Dipentamethylenethiuram hexasulfide	2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	9.1	9.0	8.9		[31.3/30.6]	31.0
R-32						
R-124	2.4	3.7	4.0		[13.2/8.5]	10.9
R-134a	-0.1	0.1	0.6		[4.0/4.2]	4.1
R-125	1.4	1.5	2.3		[5.8/5.2]	5.5
R-143a	-0.8	0.8	1.3		[4.1/4.1]	4.1
R-152a	2.5	3.6	4.0		[11.1/15.9]	13.5
R-123	23.3	22.4	22.6		[107/107]	107.0
R-142b	6.4	6.2	5.6		[21.4/21.4]	21.4
R-134	0.7	1.0	1.0		[4.9/6.1]	5.5
AB	4.2	-	[11.4/12.6]	12.0	[29.7/28.9]	29.3
MO	8.5	-	[17.2/19.9]	18.6	[53.6/54.1]	53.9
PEMA	5.5	-	[16.9/21.9]	19.4	[65.8/68.6]	67.2
PEBA	6.1	-	[16.4/14.4]	15.4	[48.7/46.2]	47.5
PPGD	0.5	-	[2.1/2.3]	2.2	[8.6/8.2]	8.4
PPGBM	0.8	-	[1.2/3.0]	2.1	[7.5/7.9]	7.7
MPG	0.1	-	[-1.8/-9.8]	-5.8	[2.9/2.7]	2.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 66

Ingredient

pphr

Polyurethane (Millable - Ester based)

100

Moca - 95% stoichiometry

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	36.9	34.4	34.8		[147/117]	132.0
R-32						
R-124	33.7	35.2	35.8		[169/145]	157.0
R-134a	3.2	3.0	3.1		[10.8/11.0]	10.9
R-125	1.2	2.2	2.3		[8.7/9.3]	9.0
R-143a	0.2	1.0	1.1		[2.7/2.8]	2.8
R-152a	4.5	4.3	4.2		[10.5/11.0]	10.8
R-123	61.9	59.4	63.9		[360/360]	360.0
R-142b	4.6	4.1	3.7		[12.1/12.3]	12.2
R-134						
AB	-0.2	-	[-0.4/-0.8]	-0.6	[-1.2/-1.1]	-1.2
MO	-0.5	-	[-1.1/-0.1]	-0.6	[-0.8/-0.4]	-0.6
PEMA	-0.7	-	[-0.1/-0.8]	-0.5	[-0.1/-0.1]	-0.1
PEBA	-0.2	-	[-0.4/-0.6]	-0.5	[-0.2/-0.2]	-0.2
PPGD	1.4	-	[5.5/6.1]	5.8	[13.8/14.5]	14.2
PPGBM	-0.4	-	[-0.4/-0.6]	-0.5	[-1.0/1.4]	0.2
MPG	-0.8	-	[-1.0/-0.1]	-0.5	[-1.6/-1.6]	-1.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 70

Ingredient	pphr
Chlorosulfonated polyethylene	100
Litharge	20
Benzothiazyl disulfide	0.5
Dipentamethylenethiuram hexasulfide	0.75
Magnesia	10
Nickel Dibutyldithiocarbamate	3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	7.8	7.2	7.3		[3.2/23.1]	23.1
R-32						
R-124	0.9	1.7	3.0		[11.1/11.1]	11.1
R-134a	-0.1	0.0	0.9		[3.6/3.5]	3.5
R-125	1.1	1.2	1.3		[3.8/3.8]	3.8
R-143a	0.7	1.3	1.9		[4.4/4.2]	4.3
R-152a	1.7	3.0	3.1		[7.6/7.5]	7.6
R-123	17.9	17.8	17.5		[71.2/71.3]	71.2
R-142b	3.9	5.9	5.7		[16.6/16.8]	16.7
R-134	0.4	0.6	0.8		[4.5/4.2]	4.4
AB	3.5	-	[8.2/7.9]	8.1	[17.4/17.8]	17.6
MO	2.6	-	[12.2/11.3]	11.8	[54.9/26.5]	30.7
PEMA	14.0	-	[34.3/31.4]	32.9	[107/99.1]	103.0
PEBA	8.1	-	[25.9/25.0]	25.5	[73.7/71.1]	72.2
PPGD	0.7	-	[1.8/2.2]	2.0	[4.9/5.4]	5.2
PPGBM	1.1	-	[1.5/1.3]	1.4	[2.7/2.9]	2.8
MPG	-0.1	-	[-0.2/-0.1]	-0.2	[0.7/0.8]	0.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 71

Ingredient	pphr
Chlorosulfonated polyethylene	100
Litharge	25
2,2'-Benzothiazyl disulfide	0.5
Dipentamethylenethiuram	2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	7.8	8.0	8.8		[26.6/26.5]	26.6
R-32						
R-124	2.9	3.7	5.1		[21.1/4.9]	13.0
R-134a	0.1	0.1	0.6		[2.2/2.3]	2.3
R-125	0.5	0.4	1.0		[2.4/2.5]	2.5
R-143a	-0.1	0.5	0.7		[2.3/2.2]	2.3
R-152a	-0.6	0.6	-1.8		[-1.6/13.7]	6.1
R-123	16.8	17.6	16.5		[68.5/68.3]	68.4
R-142b	3.1	5.1	5.7		[17.0/17.0]	17.0
R-134	0.1	0.7	-0.4		[4.0/4.0]	4.0
AB	1.1	-	[4.3/4.6]	4.5	[9.4/10.1]	9.8
MO	3.9	-	[9.2/9.5]	9.4	[22.5/23.5]	23.0
PEMA	4.7	-	[17.7/20.3]	19.0	[50.0/53.6]	51.8
PEBA	2.5	-	[10.6/11.6]	11.1	[27.2/28.7]	28.0
PPGD	0.7	-	[1.9/1.8]	1.9	[5.2/4.9]	5.1
PPGBM	0.9	-	[1.4/1.4]	1.4	[3.7/3.6]	3.7
MPG	0.2	-	[0.3/-2.5]	-1.1	[1.6/1.4]	1.5

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 72

Ingredient

pphr

EP Rubber

100

Dicumyl Peroxide

3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	mean	14 Day % Wgt. Chg.	mean
R-22	6.0	6.0	5.9		[27.6/26.9]	27.3
R-32						
R-124	2.8	3.0	2.7		[19.1/18.2]	18.7
R-134a	1.8	2.3	3.4		[10.3/5.6]	8.0
R-125	3.3	3.3	2.8		[9.2/7.6]	8.4
R-143a	1.4	1.5	0.9		[4.1/3.7]	3.9
R-152a	1.0	1.0	1.1		[5.8/5.0]	5.4
R-123	15.9	16.1	16.2		[105/105]	105.0
R-142b	7.5	7.4	7.6		[31.7]	31.7
R-134	0.6	0.6	0.1		[3.5/3.4]	3.5
AB	58.9	-	[70.7/72.8]	71.7	[434/425]	429.0
MO	66.2	-	[83.4/83.3]	83.4	[560/534]	547.0
PEMA	3.1	-	[3.2/3.1]	3.2	[12.7/12.6]	12.7
PEBA	3.2	-	[3.2/2.6]	2.9	[12.1/12.3]	12.2
PPGD	0.1	-	[0.2/0.1]	0.1	[0.4/0.3]	0.3
PPGBM	0.7	-	[0.4/0.4]	0.4	[1.5/1.6]	1.6
MPG	-0.2	-	[-0.4/-0.1]	-0.3	[-0.3/0.4]	0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 73

Ingredient

pphr

EP Rubber

100

Dicumyl Peroxide

3

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	4.5	4.4	4.5		[19.5/19.3]	19.4
R-32						
R-124	2.1	2.4	2.4		[10.8/11.3]	11.1
R-134a	0.9	1.1	0.8		[2.0/1.3]	1.7
R-125	2.2	2.1	2.1		[7.8/6.7]	7.3
R-143a	1.3	1.3	1.2		[2.7/2.6]	2.6
R-152a	1.1	1.1	1.2		[4.3/3.8]	4.1
R-123	9.1	9.0	9.0		[52.1/52.2]	52.1
R-142b	4.9	4.9	4.8		[19.8/19.5]	19.6
R-134	0.3	0.6	0.9		[2.5/2.4]	2.5
AB	41.0	-	[49.7/48.4]	49.1	[231/232]	231.0
MO	53.6	-	[58.2/59.3]	58.8	[314/317]	315.0
PEMA	2.6	-	[2.5/1.6]	2.1	[9.4/9.3]	9.4
PEBA	2.5	-	[2.8/2.4]	2.6	[9.6/9.8]	9.7
PPGD	0.8	-	[0.4/0.1]	0.3	[1.2/1.4]	1.3
PPGBM	1.3	-	[1.1/0.4]	0.7	[2.9/1.3]	2.1
MPG	0.4	-	[0.1/0.1]	0.1	[0.3/-0.1]	0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 74

Ingredient

pphr

EP Rubber

100

Dicumyl Peroxide

3

N330 Carbon Black

40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	2.7	2.8	2.6		[13.0/13.2]	13.1
R-32						
R-124	1.1	1.2	1.2		[7.1/7.4]	7.3
R-134a	0.2	0.3	0.2		[0.3/0.3]	0.3
R-125	1.8	1.8	1.7		[5.6/5.4]	5.5
R-143a	1.2	0.9	1.2		[2.4/3.1]	2.8
R-152a	0.6	0.3	0.5		[2.9/3.0]	2.9
R-123	6.8	6.6	6.1		[35.9/36.3]	36.1
R-142b	3.5	3.4	3.3		[13.6/13.3]	13.5
R-134	0.3	0.6	-0.2		[1.4/1.1]	1.3
AB	31.5	-	[36.6/36.6]	36.6	[148/147]	147.0
MO	38.5	-	[45.0/43.4]	44.2	[206/200]	203.0
PEMA	2.0	-	[1.4/1.1]	1.3	[6.0/6.0]	6.0
PEBA	1.4	-	[1.9/1.4]	1.6	[6.3/6.5]	6.4
PPGD	0.3	-	[0.1/0.1]	0.1	[0.4/0.4]	0.4
PPGBM	-0.1	-	[-0.2/0.4]	0.1	[0.8/0.9]	0.9
MPG	0.1	-	[-0.6/-0.1]	-0.4	[-0.2/-0.2]	-0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 75

Ingredient

pphr

Ethylene Acrylic Elastomer

100

Methylene Diamine

1

Diphenylguanidine

3.2

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	78.6	77.5	77.4		[116/334]	225.0
R-32						
R-124	88.8	87.3	86.3		[602/564]	585.0
R-134a	11.9	11.9	12.3		[50.7/49.6]	50.0
R-125	16.9	17.0	16.7		[74.2/74.0]	74.1
R-143a	5.3	5.5	5.5		[18.5/18.0]	18.3
R-152a	14.4	14.3	14.2		[46.4/44.9]	45.7
R-123	119.0	117.0	116.0		[1210/1190]	1200
R-142b	31.4	30.6	31.1		[130/126]	128.0
R-134	27.2	27.3	27.0		[135/128]	131.0
AB	8.1	-	[14.2/14.3]	14.3	[40.9/41.2]	41.1
MO	6.1	-	[11.0/10.6]	10.8	[31.6/31.8]	31.7
PEMA	38.8	-	[54.7/54.7]	54.7	[260/257]	259.0
PEBA	28.9	-	[51.2/51.3]	51.3	[242/233]	237
PPGD	37.5	-	[50.9/50.8]	50.9	[237/235]	236.0
PPGBM	22.0	-	[47.8/46.5]	47.2	[208/204]	206.0
MPG	19.1	-	[49.4/40.5]	45.0	[221/180]	201.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 76

Ingredient

pphr

Ethylene Acrylic Elastomer

100

N 774

35

Methylene Dianiline

1

Diphenylguanidine

4

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.		% Wgt. Chg.	
				mean		mean
R-22	47.2	46.0	46.7		[183/164]	174.0
R-32						
R-124	51.2	50.9	48.0		[277/248]	263.0
R-134a	8.5	8.3	7.9		[29.9/29.9]	29.9
R-125	11.7	12.0	11.5		[44.8/44.7]	44.7
R-143a	4.4	4.5	4.7		[10.7/10.5]	10.6
R-152a	9.4	9.5	9.5		[27.2/27.5]	27.4
R-123	65.3	66.0	69.1		[458/455]	456.0
R-142b	21.2	20.5	20.1		[81.4/78.6]	80.0
R-134	18.9	18.2	18.1		[76.6/20.1]	53.4
AB	3.9	-	[7.3/7.5]	7.4	[19.3/20.1]	19.7
MO	5.1	-	[10.2/10.1]	10.2	[24.4/24.7]	24.6
PEMA	23.7	-	[32.4/32.6]	32.5	[117/117]	117.0
PEBA	17.9	-	[31.5/30.7]	31.1	[108/107]	108.0
PPGD	23.0	-	[29.7/29.9]	29.8	[105/105]	105.0
PPGBM	14.6	-	[28.3/28.2]	28.3	[93.2/92.6]	92.9
MPG	7.6	-	[25.4/28.1]	26.8	[82.0/100]	91.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 77

Ingredient

pphr

Chlorinated Polyethylene

100

Magnesium oxide

10

Triallyl Isocyanurate

2

Dicumyl peroxide

8

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	7.0	3.7	6.8		[25.9/25.6]	25.8
R-32						
R-124	0.9	1.2	2.6		[6.4/6.8]	6.6
R-134a	0.2	0.1	0.8		[3.1/2.5]	2.8
R-125	0.2	0.2	0.7		[3.0/2.8]	2.9
R-143a	0.3	0.5	1.0		[2.4/2.5]	2.5
R-152a	0.8	2.0	1.9		[11.0/10.2]	10.6
R-123	15.8	15.0	14.9		[22.4/22.8]	22.6
R-142b	3.1	4.8	4.9		[7.2/7.0]	7.1
R-134	0.1	0.2	0.5		[3.1/3.4]	3.3
AB	1.9	-	[7.5/7.4]	7.5	[18.5/18.7]	18.6
MO	4.9	-	[13.8/12.9]	13.4	[39.1/34.8]	36.9
PEMA	6.6	-	[21.6/21.2]	21.4	[63.8/68.8]	66.3
PEBA	3.5	-	[13.2/14.0]	13.6	[40.3/43.0]	41.7
PPGD	0.4	-	[1.6/1.4]	1.5	[4.6/4.3]	4.5
PPGBM	0.3	-	[1.2/1.1]	1.2	[3.8/3.6]	3.7
MPG	0.1	-	[0.2/0.2]	0.2	[0.5/1.0]	0.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 78

Ingredient	pphr
Chlorinated PE	100
Magnesium Dioxide	10
Triallyl Isocyanurate	2
Dicumyl Peroxide on Clay	4
N330 Carbon Black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	4.7	4.2	4.5	[18.6/18.4] 18.5
R-32				
R-124	0.0	0.4	1.3	[7.5/7.3] 7.4
R-134a	0.2	0.3	0.6	[2.2/2.0] 2.1
R-125	0.0	0.3		[2.2/2.1] 2.2
R-143a	-0.1	0.2	0.5	[1.7/1.8] 1.8
R-152a	1.1	2.0	2.0	[4.7/4.9] 4.8
R-123	10.2	11.7	10.2	[49.0/49.5] 49.2
R-142b	1.0	3.5	3.8	[12.6/12.6] 12.6
R-134	0.1	0.2	0.4	[1.7/2.2] 2.0
AB	3.1	-	[9.9/9.4] 9.7	[25.8/25.4] 25.6
MO	1.8	-	[6.4/6.5] 6.5	[14.5/14.8] 14.7
PEMA	5.7	-	[14.2/13.8] 14.0	[42.0/40.8] 41.4
PEBA	2.1	-	[11.1/10.7] 10.9	[31.6/30.2] 30.9
PPGD	0.6	-	[1.3/1.6] 1.5	[4.0/4.1] 4.1
PPGBM	0.2	-	[1.0/1.0] 1.0	[2.1/2.0] 2.1
MPG	0.4	-	[-0.1/-0.1] -0.1	[0.1/0.1] 0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 79

Ingredient

pphr

Chlorinated Polyethylene

100

Magnesium oxide

10

Triallyl Isocyanurate

2

Dicumyl peroxide

8

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day	
			% Dia. Chg.	mean	% Wgt. Chg.	mean
R-22	5.4	5.3	5.0		[18.6/18.8]	18.7
R-32						
R-124	0.6	0.8	0.8		[4.2/3.7]	4.0
R-134a	0.0	-0.1	-0.1		[0.5/0.9]	0.7
R-125	0.0	0.6	0.8		[1.9/2.5]	2.2
R-143a	0.0	0.4	0.3		[0.6/0.6]	0.6
R-152a	1.4	1.9	2.3		[5.1/6.2]	5.7
R-123	9.8	10.2	9.8		[47.2/46.2]	46.7
R-142b	1.7	2.6	3.4		[12.7/13.3]	13.0
R-134						
AB						
MO	-1.2	-	[5.6/5.7]	5.7	[14.3/15.8]	15.1
PEMA	8.3	-	[31.7/34.5]	33.1	[119/131]	125.0
PEBA	6.6	-	[23.2]	23.2	[78.2]	78.2
PPGD	0.2	-	[0.1/0.7]	0.4	[2.0/2.1]	2.1
PPGBM	-0.3	-	[-0.2/-0.2]	-0.2	[1.3/1.0]	1.2
MPG						

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #80

Ingredient

pphr

EPDM	100
Zinc Oxide	5
Sulfur	15
Stearic Acid	1
TMTD	1
MBT	0.5

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	3.9	4.3	3.8		[16.7/16.0]	16.4
R-32						
R-124	1.7	2.2	2.1		[10.2/10.6]	10.4
R-134a	0.5		0.6		[2.4/2.5]	2.5
R-125	2.3	2.9	2.8		[9.0/9.0]	9.0
R-143a	1.0	0.9	0.7		[2.7/2.4]	2.6
R-152a	1.1	1.0	0.9		[4.0/3.6]	3.8
R-123	7.9	8.8	8.8		[46.5/46.4]	46.5
R-142b	3.7	3.6	3.9		[15.3/15.5]	15.4
R-134	0.5	0.8	0.6		[2.6/2.5]	2.6
AB	30.3	-	[35.8/35.6]	35.7	[142/141]	142.0
MO	37.6	-	[42.4/42.2]	42.3	[186/185]	186.0
PEMA	2.7	-	[2.3/2.3]	2.3	[7.1/7.4]	7.3
PEBA	1.9	-	[2.3/2.4]	2.4	[8.2/8.0]	8.1
PPGD	0.3	-	[0.2/0.0]	0.1	[0.1/0.2]	0.2
PPGBM	0.9	-	[0.2/0.6]	0.4	[1.5/1.6]	1.6
MPG	-0.9	-	[-0.2/-0.3]	-0.3	[0.2/0.1]	0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 81

Ingredient	pphr
EPDM	100
Zinc Oxide	5
Sulfur	1.5
Stearic Acid	1
TMTD	1
MBT	0.5

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg. mean	14 Day % Wgt. Chg. mean
R-22	5.5	5.3	5.0	[24.3/23.8] 24.1
R-32				
R-124	3.1	3.8	3.5	[15.5/19.1] 17.3
R-134a	0.9		0.7	[3.7/3.8] 3.8
R-125	3.8	3.6	3.6	[11.5/10.9] 11.2
R-143a	1.1	1.2	1.0	[5.0/4.5] 4.8
R-152a	1.4	1.6	1.6	[5.6/5.9] 5.8
R-123	14.6	14.6	14.5	[79.3/79.6] 79.5
R-142b	6.3	6.3	6.1	[25.5/25.3] 25.4
R-134	0.3	0.8	-0.6	[4.1/3.6] 3.9
AB	28.5	-	[35.6/37.1] 36.4	[149/148] 148.0
MO	32.0	-	[41.7/42.6] 42.2	[188/188] 188.0
PEMA	2.6	-	[3.2/3.2] 3.2	[10.6/10.6] 10.6
PEBA	2.2	-	[3.4/3.3] 3.4	[11.1/10.9] 11.0
PPGD	0.5	-	[-0.6/-0.1] -0.4	[0.3/0.6] 0.5
PPGBM	0.5	-	[-0.3/0.6] 0.2	[2.2/2.4] 2.3
MPG	0.3	-	[0.2/0.2] 0.2	[0.8/0.9] 0.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #82

Ingredient	pphr
EPDM	100
Zinc Oxide	5
Sulfur	1.5
Stearic Acid	1
TMTD	1
MBT	0.5

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	4.4	4.9	4.5		[19.0/18.5]	18.8
R-32						
R-124	2.2	2.5	2.5		[12.5/12.1]	12.3
R-134a	0.3	0.3	0.2		[2.9/2.9]	2.9
R-125	2.6	3.5	3.3		[10.6/9.5]	10.1
R-143a	0.8	0.7	0.6		[3.4/3.4]	3.4
R-152a	1.3	1.3	1.3		[4.0/5.2]	4.6
R-123	10.0	9.8	9.6		[56.4/56.2]	56.3
R-142b	4.9	5.0	5.1		[19.5/19.1]	19.3
R-134	0.6	0.9	0.6		[2.9/2.6]	2.8
AB	28.4	-	[35.1/34.9]	35.0	[143/143]	143.0
MO	35.9	-	[41.9/41.8]	41.9	[184/186]	185.0
PEMA	2.8	-	[2.4/2.3]	2.4	[7.4/7.4]	7.4
PEBA	1.5	-	[2.2/2.3]	2.3	[8.0/7.9]	8.0
PPGD	0.2	-	[0.2/-0.4]	-0.1	[0.1/0.0]	0.1
PPGBM	0.4	-	[-0.5/1.1]	0.5	[1.6/1.6]	1.6
MPG	0.2	-	[0.0/0.0]	0.0	[0.2/0.1]	0.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #83

Ingredient	pphr
EPDM	100
Zinc Oxide	5
Sulfur	1.5
Stearic Acid	1
TMTD	1
MBT	0.5
N330 Carbon Black	40

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day		14 Day	
			% Dia. Chg.	mean	% Wgt. Chg.	mean
R-22	3.1	3.4	2.8		[11.3/11.2]	11.3
R-32						
R-124	1.3	1.8	1.5		[7.1/7.1]	7.1
R-134a	0.2		0.7		[1.5/1.7]	1.6
R-125	1.7	2.6	2.5		[7.4/7.4]	7.4
R-143a	0.8	0.6	0.4		[2.1/1.9]	2.0
R-152a	1.0	1.0	0.8		[3.5/2.6]	3.1
R-123	6.5	6.3	6.5		[32.6/32.4]	32.5
R-142b	3.8	3.8	3.4		[11.1/10.9]	11.0
R-134	0.3	-0.3	0.7		[1.4/2.0]	1.7
AB	20.6	-	[26.8/25.3]	26.1	[85.8/85.6]	85.7
MO	25.9	-	[29.4/29.8]	29.6	[113/112]	112.0
PEMA	0.6	-	[1.3/1.5]	1.4	[5.3/5.3]	5.3
PEBA	1.5	-	[1.8/1.5]	1.7	[5.4/5.7]	5.6
PPGD	0.3	-	[0.4/0.5]	0.5	[0.3/0.2]	0.3
PPGBM	0.6	-	[1.1/0.0]	0.6	[1.3/1.2]	1.3
MPG	0.1	-	[0.2/0.1]	0.2	[0.1/0.2]	0.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 84

Ingredient

pphr

EPDM	100
Zinc Oxide	5
Stearic Acid	1
Dicumyl Peroxide	1

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	mean	mean
R-22	4.3	4.3	4.0	[19.7/19.8]	19.8
R-32					
R-124	2.4	2.5	2.4	[12.8/12.3]	12.6
R-134a	0.5	0.6	0.6	[2.2/2.2]	2.2
R-125	2.6	3.1	2.7	[9.8/8.7]	9.3
R-143a	0.7	0.8	0.8	[3.2/3.1]	3.2
R-152a	1.3	1.1	1.2	[4.5/4.2]	4.4
R-123	9.9	10.1	9.9	[55.4/55.5]	55.5
R-142b	4.7	4.7	4.4	[19.1/18.6]	18.8
R-134	0.6	0.9	0.8	[3.3/3.2]	3.3
AB	48.5	-	[59.0/59.5] 59.3	[285/286]	285.0
MO	61.8	-	[72.8/72.3] 72.6	[412/403]	407.0
PEMA	3.0	-	[2.6/2.5] 2.6	[8.7/6.8]	7.8
PEBA	0.5	-	[2.6/2.6] 2.6	[9.8/9.8]	9.8
PPGD	0.8	-	[0.5/0.9] 0.7	[1.9/1.8]	1.9
PPGBM	1.0	-	[0.7/0.9] 0.8	[2.5/2.4]	2.5
MPG	0.5	-	[0.1/0.2] 0.2	[0.9/0.8]	0.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula # 85

Ingredient

pphr

Butyl/Polypropylene TPE

100

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22						
R-32						
R-124	0.4	-0.2	-1.8		[-0.7/0.7]	0.0
R-134a	0.2	0.3	0.3		[2.7/2.7]	2.7
R-125	1.8	2.0	2.3		[10.0/8.3]	9.2
R-143a	0.3	0.3	0.5		[3.2/3.8]	3.5
R-152a	-0.3	-0.7	-1.4		[-1.5/0.1]	-0.8
R-123	2.1	1.9	2.4		[33.7/33.7]	33.7
R-142b	0.3	-1.2	-2.4		[-1.2/-0.8]	-1.0
R-134	0.4	0.8	0.7		[3.4/3.2]	3.3
AB	11.9	-	[20.5/20.9]	20.7	[87.4/85.1]	86.3
MO	16.7	-	[2507/25.1]	25.4	[114/112]	113.0
PEMA	-2.6	-	[-2.9/-2.9]	-2.9	[-6.4/-6.1]	-6.3
PEBA	-2.0	-	[-3.2/-3.5]	-3.4	[6.4/-6.1]	0.2
PPGD	-2.8	-	[-5.7/-5.5]	-5.6	[-15.9/-15.7]	-15.8
PPGBM	-2.4	-	[-5.8/-5.4]	-5.6	[-15.7/-14.5]	-15.1
MPG	-1.6	-	[-4.9/-4.8]	-4.9	[-14.7/-14.9]	-14.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #86

Ingredient

pphr

Chloroprene Rubber (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day		
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.		
			mean		mean	
R-22	0.3	-0.6	-0.8	[2.1/2.3]	2.2	
R-32						
R-124	1.3	0.8	-1.3	[2.6/3.0]	2.8	
R-134a	-0.6	-1.5	-2.6	[-4.8/-4.8]	-4.8	
R-125	-0.3	-0.9	-2.2	[-4.0/-4.0]	-4.0	
R-143a	-0.8	-1.6	-2.5	[-5.2/-5.2]	-5.2	
R-152a	-1.3	-2.0	-3.1	[-5.2/-5.2]	-5.2	
R-123	5.7	5.5	4.9	[24.1/23.7]	23.9	
R-142b	0.1	-1.2	-1.5	[92.2/107]	99.4	
R-134	-0.9	-1.2	-2.0	[-1.9/-1.4]	-1.7	
AB	2.8	-	[5.8/3.7]	4.8	[12.1/12.0]	12.1
MO	2.3	-	[3.4/3.6]	3.5	[6.1/6.1]	6.1
PEMA	6.4	-	[8.7/8.9]	8.8	[21.1/21.0]	21.1
PEBA	1.7	-	[6.2/6.4]	6.3	[15.0/14.8]	14.9
PPGD	-0.7	-	[-0.6/-0.6]	-0.6	[-0.2/-0.2]	-0.2
PPGBM	-0.7	-	[1.3/1.3]	1.3	[2.9/3.0]	3.0
MPG	-2.4	-	[0.7/-1.9]	-0.6	[-3.5/-3.0]	-3.3

PEMA - Pentaerythritol Ester Mixed Acid

PEBA - Pentaerythritol Ester Branched Acid

PPGBM - Polypropylene Glycol Butyl Monoether

MO - Mineral Oil

MPG - Modified Polyglycol

PPGD - Polypropylene Glycol Diol

AB - Alkyl Benzene

Formula #87

Ingredient

pphr

ACN Compound (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	23.8	23.7	23.9	118/106 112
R-32				
R-124	21.1	21.1	20.5	[111/101] 106.0
R-134a	1.7	1.6	1.3	6.7/7.1 6.9
R-125	1.9	2.5	2.1	8.2/8.9 8.5
R-143a	0.7	1.3	1.3	2.6/2.7 2.7
R-152a	3.3	2.8	2.6	[8.0/8.0] 8.0
R-123	42.5	40.7	39.9	238/237 238
R-142b	5.1	3.9	3.8	16.4/17.0 16.7
R-134	7.1	7.1	6.8	[29.6/30.0] 29.8
AB	0.4	-	[1.0/1.2] 1.1	[1.7/2.0] 1.9
MO	-0.3	-	[0.1/0.1] 0.1	[-0.7/-0.9] -0.8
PEMA	1.5	-	[4.0/4.1] 4.1	[11.3/11.2] 11.3
PEBA	1.0	-	[3.1/3.0] 3.1	[8.0/7.9] 8.0
PPGD	1.2	-	[1.9/1.6] 1.8	[4.3/4.3] 4.3
PPGBM	-0.6	-	[-0.6/-0.8] -0.7	[-2.6/-2.3] -2.5
MPG	-0.7	-	[-1.5/-1.7] -1.6	[-4.7/-4.5] -4.6

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #88

Ingredient

pphr

Neoprene/Synthetic Fiber Compound (Vendor Supplied Cured Sheets)

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.	14 Day % Wgt. Chg.
R-22	-0.5	0	-0.6	[10.8/8.7] 9.8
R-32				
R-124	0.0	0.0	0.2	[13.0/7.7] 10.4
R-134a	0.5	-0.3	-0.4	[11.5/8.4] 10.0
R-125	0.3	0.4	-0.1	[9.1/7.1] 8.1
R-143a	0.2	0	-0.5	[5.4/3.7] 4.6
R-152a	-0.4	-0.2	-0.4	[7.5/4.9] 6.2
R-123	1.3	0.7	1.1	[17.7/17.5] 17.6
R-142b	0	-0.3	-0.4	[11.9/7.2] 9.6
R-134	-0.1	0.5	0.3	[12.0/10.5] 11.3
AB	-0.3	-	[0.1/0.6] 0.4	[12.7/12.9] 12.8
MO	0.6	-	[0.8/-0.1] 0.4	[10.0/10.6] 10.3
PEMA	0.8	-	[1.1/0.1] 0.6	[16.6/16.0] 16.3
PEBA	0.2	-	[0.3/0.1] 0.2	[13.6/13.3] 13.5
PPGD	-1.0	-	[-0.1/0.6] 0.3	[11.6/11.2] 11.4
PPGBM	2.2	-	[1.5/8.3] 4.9	[11.1/11.0] 11.1
MPG	0.3	-	[0.3/0.1] 0.2	[10.8/11.2] 11.0

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #89

Ingredient

pphr

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Dia. Chg.		14 Day % Wgt. Chg.	
			mean		mean	
R-22	0.0	-0.1	-0.4		[58.1/31.8]	44.9
R-32						
R-124	0.1	0.2	0.2		[69.6/28.1]	48.9
R-134a	0.3	0.3	-0.1		[37.3/19.0]	28.2
R-125	0.2	0.2	0.2		[3.7/2.0]	2.9
R-143a	-0.3	0.4	0.2		[13.5/2.4]	8.0
R-152a	0.2	0.4	0.2		[23.5/9.4]	16.5
R-123	0.4	0.5	0.0		[95.6/95.6]	95.6
R-142b	0.4	-0.1	-0.1		[35.7/29.4]	32.6
R-134	0.3	0.1	0.1		[48.8/30.7]	39.8
AB	2.5	-	[2.1/0.4]	1.3	[22.2/20.9]	21.6
MO	-0.2	-	[-0.4/0.1]	-0.2	[24.3/23.6]	24.0
PEMA	-0.2	-	[-0.1/0.2]	-0.1	[27.9/26.8]	27.4
PEBA	0.2	-	[-0.1/-0.2]	-0.2	[27.2/28.0]	27.6
PPGD	-0.6	-	[0.1/-0.2]	-0.1	[33.9/34.6]	34.3
PPGBM	-0.4	-	[-0.2/-0.1]	-0.1	[26.4/27.7]	27.1
MPG	-0.4	-	[-0.5/-0.2]	-0.4	[29.1/27.1]	28.1

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #90

Ingredient

pphr

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg. mean	mean
R-22	0.1	0.1	-0.6	[70.4/21.4]	45.9
R-32					
R-124	0.6	1.0	0.8	[39.4/17.6]	28.5
R-134a	0.0	0.1	-0.1	[17.5/0.6]	9.1
R-125	-0.1	-0.1	0.1	[13.7/2.2]	7.9
R-143a	-0.1	0.1	-0.3	[7.2/0.8]	4.0
R-152a	0.3	0.3	0.1	[27.2/-1.2]	13.0
R-123	0.5	0.0	0.6	[121/135]	128.0
R-142b	-0.3	0.2	0.1	[20.1/14.1]	17.1
R-134	0.5		-0.2	[32.0/9.1]	20.6
AB	-0.1	-	[-0.5/0.1]	-0.2	[17.6/12.3]
MO	-0.4	-	[-0.2/-0.1]	-0.1	[17.9/22.2]
PEMA	-0.2	-	[0.1/-0.2]	-0.1	[26.7/28.8]
PEBA	0.1	-	[-0.2/-0.3]	-0.3	[23.6/23.7]
PPGD	0.1	-	[0.1/-0.1]	0.0	[22.8/27.8]
PPGBM	-0.4	-	[-0.1/-0.2]	0.1	[22.8/19.6]
MPG	-1.0	-	[-0.5/0.1]	-0.2	[22.6/22.0]

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #91

Ingredient

pphr

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg. mean	mean	
R-22	23.0	23.1	23.0	[11.9/4.4]	8.2
R-32					
R-124	-2.8	-2.1	-2.9	[7.9/15.7]	11.8
R-134a	-0.1	-0.1	-0.2	[9.3/5.3]	7.3
R-125	0.1	0.3	0.1	[1.9/1.0]	1.5
R-143a	-0.2	0.0	-0.2	[7.0/1.9]	4.5
R-152a	2.9	3.1	2.6	[15.2/-0.4]	7.4
R-123	0.5	0.7	0.7	[19.0/19.1]	19.1
R-142b	0.5	0.4	0.4	[12.1/11.4]	11.8
R-134					
AB	0.5	-	[.5/0.5] 0.5	[12.4/12.1]	12.3
MO	0.7	-	[0.7/0.5] 0.6	[13.2/13.7]	13.5
PEMA	0.4	-	[0.7/0.5] 0.6	[14.8/14.6]	14.7
PEBA	0.9	-	[0.6/4.1] 2.4	[14.0/14.3]	14.2
PPGD	0.5	-	[0.4/0.5] 0.5	[13.1/12.6]	12.9
PPGBM	1.0	-	[0.6/6.2] 3.4	[13.5/13.4]	13.5
MPG	0.5	-	[0.3/0.5] 0.4	[12.0/12.4]	12.2

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #92

Ingredient

pphr

Swell Data:

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Wgt. Chg. mean	14 Day mean
R-22	4.0	2.8	1.9	{30.3/13.2} 21.8
R-32				
R-124	1.8	1.9	1.8	{30.2/16.5} 23.4
R-134a	-0.1	0.5	0.1	{8.5/4.5} 6.5
R-125	0.5	0.4	0.1	{2.5/1.7} 2.1
R-143a	0.6	0.2	0.4	{3.8/1.4} 2.6
R-152a	0.9	0.9	0.8	{8.8/3.2} 6.0
R-123	5.0	0.4	4.4	{53.5/54.9} 54.2
R-142b	7.2	7.0	1.0	{11.8/11.1} 11.5
R-134				
AB	0.6	-	{0.2/0.5} 0.4	{7.5/6.9} 7.2
MO	0.5	-	{0.4/0.6} 0.5	{10.6/10.5} 10.6
PEMA	1.1	-	{-0.8/1.2} 0.2	{11.7/11.5} 11.6
PEBA	0.5	-	{0.7/0.5} 0.6	{10.2/10.3} 10.3
PPGD	0.8	-	{0.7/}	{21.5/22.2} 21.9
PPGBM	0.3	-	{0.1/0.1} 0.1	{9.7/9.1} 9.4
MPG	0.7	-	{0.3/0.2} 0.3	{8.8/9.0} 8.9

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #93

Ingredient

pphr

Swell Data

Test Fluid	24 Hour	72 Hour	14 Day	14 Day	
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg. mean	mean
R-22	0.6	0.6	0.6	[-0.1/-0.2]	-0.2
R-32					
R-124	0.4	0.4	0.4	[36.0/14.0]	25.0
R-134a	-0.1	0.3	0.1	[15.1/1.2]	8.2
R-125	0.3	0.4	0.1	[1.8/1.2]	1.5
R-143a	-0.4	-2.7	-0.3	[1.2/0.6]	0.9
R-152a	-0.3	-0.1	0.1	[16.0/1.9]	9.0
R-123	0.5	0.2	0.5	[60.2/60.2]	60.2
R-142b	-0.4	-0.1	-0.4	[18.0/15.8]	16.9
R-134					
AB	-0.1	-	[-0.1/-0.1]	-0.1	[16.0/15.9]
MO	0.2	-	[-0.1/-0.1]	-0.1	[20.3/18.5]
PEMA	0.4	-	[0.1/0.2]	0.2	[20.2/18.7]
PEBA	-4.0	-	[0.1/2.0]	1.1	[18.5/18.2]
PPGD	0.1	-	[-0.1/0.1]	0.0	[21.5/22.2]
PPGBM	0.5	-	[0.1/2.2]	1.2	[19.0/21.2]
MPG	0.4	-	[-0.1/0.3]	0.1	[19.7/18.7]

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #94

Ingredient

pphr

Swell Data:

Test Fluid	24 Hour	72 Hour	14 Day		14 Day
	% Dia. Chg.	% Dia. Chg.	% Dia. Chg.	% Wgt. Chg.	
			mean		mean
R-22	25.8	24.2	23.4		[68.6/65.0] 66.8
R-32					
R-124	20.9	2.5	20.7		[66.0/58.5] 62.3
R-134a	19.1	20.7	20.3		[53.0/51.0] 52.0
R-125	10.1	10.0	1.0		[27.1/26.4] 26.8
R-143a	11.7	12.2	11.8		[25.6/25.5] 25.6
R-152a	29.1	28.8	30.2		[57.9/54.7] 56.3
R-123	21.8	21.7	23.2		[69.0/69.1] 69.1
R-142b	26.3	23.8	23.8		[58.3/57.0] 57.7
R-134					
AB	0.1	-	[0.1/0.1] 0.1		[0.5/0.3] 0.4
MO	-0.5	-	[0.1/0.2] 0.2		[2.4/2.3] 2.4
PEMA	1.1	-	[3.0/3.7] 3.4		[7.5/7.6] 7.6
PEBA	1.5	-	[7.3/9.3] 8.3		[14.6/14.8] 14.7
PPGD	0.6	-	[1.1/0.8] 1.0		[2.1/2.2] 2.2
PPGBM	-0.1	-	[-0.2/0.1] -0.1		[0.8/0.8] 0.8
MPG	0.2	-	[0.1/0.1] 0.1		[0.5/0.3] 0.4

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

Formula #95

Ingredient

pphr

Swell Data

Test Fluid	24 Hour % Dia. Chg.	72 Hour % Dia. Chg.	14 Day % Wgt. Chg. mean	14 Day mean
R-22	6.5	5.5	5.5	[16.8-16.4] 16.6
R-32				
R-124	0.5	1.5	2.5	[9.0-9.4] 9.2
R-134a	0.1	0.1	0.3	[1.0-1.2] 1.1
R-125	-0.4	0.1	-0.2	[0.2-0.6] 0.4
R-143a	0.1	0.2	0.1	[0.3-0.2] 0.3
R-152a	2.5	2.1	1.7	[2.5-2.8] 2.7
R-123	10.1	8.8	9.1	[29.0-29.8] 29.4
R-142b	1.9	2.4	1.8	[4.1-4.6] 4.3
R-134				
AB	-0.9	-	[-0.6/-0.8] -0.7	[-1.7-1.9] -1.8
MO	-1.2	-	[-1.4/-0.6] -1.0	[-1.0-0.8] -0.9
PEMA	2.0	-	[11.8-12.0] 11.9	[26.6-26.5] 26.6
PEBA	1.6	-	[7.9-7.2] 7.6	[16.8-17.0] 16.9
PPGD	2.5	-	[8.4-7.4] 7.9	[17.0-17.6] 17.3
PPGBM	0.0	-		[0.2-0.2] 0.2
MPG	-0.7	-	[-0.9/-0.8] -0.9	[-1.8-1.7] -1.8

PEMA - Pentaerythritol Ester Mixed Acid
 PEBA - Pentaerythritol Ester Branched Acid
 PPGBM - Polypropylene Glycol Butyl Monoether
 MO - Mineral Oil

MPG - Modified Polyglycol
 PPGD - Polypropylene Glycol Diol
 AB - Alkyl Benzene

APPENDIX B

TEST METHODOLOGY

- Mixing:** Most of the formulations tested in this study were mixed on a laboratory size rubber mill. The base polymer was milled for a short period of time to allow the normal breakdown of the elastomer. The ingredients were then added to the elastomer on the 2 roll mill in the order they appear in the compound recipe. The materials are mixed thoroughly until the rubber compound appears to be homogeneous.
- Cure Characteristics:** The cure time for each of the formulations is determined using normal cure temperature ranges as suggested by the manufacturers or temperatures commonly used by the rubber industry. The oscillating disk rheometer (ODR) is used to determine the cure characteristics of the compound in question at the appropriate temperature.
- The ODR is used to obtain information concerning the state of cure of the formulation with time. This instrument produces a cure curve (torque vs. time) and the cure time to 95 % of the maximum torque is calculated from this graph. All test compounds formulated at the University of Akron were cured into sheets at the T_{95} % cure level.
- Other Compounds:** The thermoplastic elastomer materials were either tested as received (when received in sheet form) or injection molded when received in pellet form.
- Gasket materials received from vendors were tested as received.
- Sample Preparation:** Sheet materials were placed on a vacuum table attached to a drill press fitted with a cutter assembly. The cutter assembly consists of a holder and a stainless steel blade. The machine was turned on and the cutter lowered so as to cut through the rubber sheet. Round disk-like samples were prepared in this manner for the swell tests.

Measurements: Diameter measurements were obtained using a travelling microscope.

Thickness measurements were obtained using a thickness gauge.

Weight measurements were obtained using an analytical balance.

Lubricant Swell: The round disk samples were measured (2 each test) and placed in 2 oz. jars with lids, the predried lubricants were poured into each of the containers and sealed. The containers were placed in an oven at 60 degrees centigrade.

Diameter measurements on the top most sample were taken at 1 day and 14 days. Weight, thickness and diameter measurements were taken on both samples at 14 days.

Refrigerant Swell: The round disk-like samples were measured (2 each test) and placed in the bottom of the refrigerant test vessel (figure 4). Stainless steel screens were placed in between the samples so that the samples could be differentiated from each other. They also acted as weights to submerge the rubber disks.

The test vessels were closed using a hydraulic press to compress the die springs. The springs maintained a constant force (2500 lbs.) on the Teflon O-Ring such that the volatile refrigerant gases were contained in the vessel.

Test vessels were filled with refrigerant by first pulling a vacuum in the chamber. The refrigerant valve was then opened and refrigerant was allowed to fill the chamber to a mark slightly above the samples.

In situ diameter changes were taken at 1 day, 3 day and 14 days through the use of a travelling microscope and microscope lights. These measurements were made possible by the use of a glass/polycarbonate window in the top of the test vessel.

FIGURE 4

TEST VESSEL IN SITU DIAMETER CHANGE MEASUREMENTS

APPENDIX C

Vendor Supplied Gasket Material Formulation Numbers

Formula # 86 Precision Rubber Products #2167

Formula # 87 Precision Rubber Products #7507

Formula # 88 Garlock 2930

Formula # 89 Armstrong N-8092

Formula # 90 Specialty Paperboard NI-2085G

Formula # 91 Victopac 69

Formula # 92 Klingersil C-4401

Formula # 93 Specialty Paperboard NI-2099

Formula # 94 Parker V747-75

Formula # 95 Green Tweed 956

Addendum to

Compatibility of Refrigerants and Lubricants with Elastomers

Quarterly Report: 1 July 1992 – 30 September 1992

October 1992

Lubricants Utilized in the Research

mineral oil

MO	naphthenic mineral oil	Witco Suniso 3GS (32 cSt)
----	------------------------	---------------------------

alkylbenzene

AB	alkylbenzene	Shrieve Zerol ^(R) 150 (32 cSt)
----	--------------	---

polyglycols

PPGBM	polypropylene glycol butyl monoether	ICI Emkarox ^(R) (32 cSt)
PPGD	polypropylene glycol diol	Dow P425 (32 cSt)
MPG	modified polyglycol	Allied-Signal BRL-150 (32 cSt)

polyolesters

PEMA	pentaerythritol ester mixed acid	ICI Emkarate ^(R) RL 244 (22 cSt)
PEBA	penta erythritol ester branched-acid	Emery 2927-A (32 cSt)

END

**DATE
FILMED**

2 / 10 / 93