10/1-9-92 GSD

ORNL-6650

**OAK RIDGE
NATIONAL
LABORATORY**

MARTIN MARIETTA

**Fossil Energy Program
Semiannual Progress Report
for April 1990 Through
September 1990**

R. R. Judkins

**MANAGED BY
MARTIN MARIETTA ENERGY SYSTEMS, INC.
FOR THE UNITED STATES
DEPARTMENT OF ENERGY**

*Fossil
Energy
Program*

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ORNL--6650

DE92 004596

Fossil Energy Program

FOSSIL ENERGY PROGRAM SEMIANNUAL PROGRESS REPORT
FOR APRIL 1990 THROUGH SEPTEMBER 1990

R. R. Judkins
Program Manager

Date Published: September 1991

Prepared for the
DOE Office of Fossil Energy
(AA 15 10 10 0)

Prepared by the
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U.S. DEPARTMENT OF ENERGY
under Contract DE-AC05-84OR21400

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

REPORTS PREVIOUSLY ISSUED IN THIS SERIES

Previous reports in this series included quarterly and semiannual publications. A complete listing of these reports through March 1989 is given in ORNL-6617.

ORNL-6486, Fossil Energy Program Semiannual Progress Report for
October 1987 Through March 1988

ORNL-6522, Fossil Energy Program Semiannual Progress Report for
April 1988 Through September 1988

ORNL-6562, Fossil Energy Program Semiannual Progress Report for
October 1988 Through March 1989

ORNL-6617, Fossil Energy Program Semiannual Progress Report for
April 1989 Through September 1989

ORNL-6634, Fossil Energy Program Semiannual Progress Report for
October 1989 Through March 1990

CONTENTS

ABSTRACT	1
1. SUMMARY	1
1.1 MATERIALS RESEARCH AND DEVELOPMENT	1
2. MATERIALS RESEARCH AND DEVELOPMENT	5
2.1 ENVIRONMENTAL ANALYSIS AND INFORMATIONAL SYSTEMS	6
2.1.1 Fabrication of Fiber-Reinforced Composites	7
2.1.1.1 Background	7
2.1.1.2 Approach	7
2.1.1.3 Discussion of Current Activities	8
2.1.2 Interfaces and Mechanical Properties of Continuous Fiber-Reinforced Ceramic Composites	10
2.1.2.1 Background	11
2.1.2.2 Approach	11
2.1.2.3 Oxidation and Corrosion of Nicalon/Sic Composites	12
2.1.2.4 Experimental	13
2.1.2.5 Characterization	16
2.1.2.6 Oxidation	16
2.1.2.7 Corrosion	20
2.1.2.8 Interfacial Shear Stress Measurements	21
2.1.2.9 Alternate Coatings	23
2.1.3 Ceramic Fiber-Ceramic Matrix Hot-Gas Filters	25
2.1.3.1 Background	25
2.1.3.2 Approach	26
2.1.3.3 Discussion of Current Activities	26
2.1.4 Gas Separations Using Inorganic Membranes	28

2.1.4.1	Background	29
2.1.4.2	Approach	29
2.1.4.3	Discussion of Current Activities	30
2.1.5	Microwave Sintering of Materials for Fuel Cells	33
2.1.5.1	Sintering of LaCrO_3 Materials	33
2.1.5.2	Evaluation of Substitute Insulation Materials for Microwave Processing	37
2.2	NEW ALLOYS	41
2.2.1	Environmental Effects on Iron Aluminides	41
2.2.1.1	Discussion of Current Activities	41
2.2.2	Investigation of Austenitic Alloys for Advanced Heat Recovery and Hot-Gas Cleanup Systems	44
2.2.2.1	Identification of Materials for Hot Gas Filter Tubesheets	46
2.2.3	Development of Iron Aluminides	52
2.2.3.1	Effect of Chromium on Minimizing Environmental Embrittlement	52
2.2.3.2	Effect of Surface Condition on Tensile Properties	54
2.2.3.3	Measurement of Electrical Resistivity	56
2.2.3.4	Weldability	58
2.2.3.5	Fabrication	62
2.2.3.6	Fracture Testing of FA-129 Alloy	66
2.2.3.7	Technology Transfer Activities	70
2.2.3.7.1	Ford Motor Company	70
2.2.3.7.2	Dresser-Rand Corporation	70
2.2.3.7.3	PALL-Trinity	70
2.2.3.7.4	Ametek Special Products Division	71

2.2.3.7.5	Wisconsin Centrifugal	71
2.2.3.7.6	Kiln Applications	71
2.2.3.7.7	Air Products and Chemicals	71
2.2.3.7.8	The Timken Company	72
2.2.3.7.9	Harrison Alloys	72
2.2.3.7.10	Precision Rolled Products	72
2.2.3.7.11	Others	73
2.3	CORROSION AND EROSION RESEARCH	74
2.3.1	Responses of Metallic and Oxide Surfaces to Deformation	74
2.3.1.1	Erosion Studies	74
2.3.1.2	Erosion Behavior of 1100 Al and Fe ₃ Al Alloys	74
2.3.1.3	Single-Particle Impact Studies to Determine Effect of Energy Input on Erosion of 1100 Al and Fe ₃ Al Alloys	81
2.3.1.4	Single-Particle Impact Characterization of Erosion-Corrosion Scales on Steels	85
2.3.2	Mechanical Properties Of Oxide Scales	92
2.4	TECHNOLOGY ASSESSMENT AND TECHNOLOGY TRANSFER	96
2.4.1	Coal Conversion and Utilization Plant Support Services	96
2.5	REFERENCES	96
3.	ENVIRONMENTAL ANALYSIS AND INFORMATION SYSTEMS	99
3.1	ENVIRONMENTAL SUPPORT TO THE CLEAN COAL PROGRAM	99
4.	COAL CONVERSION DEVELOPMENT	103
4.1	BIOLOGICAL COAL CONVERSION	103
4.1.1	Background	104
4.1.1.1	Anaerobic Microbial Coal Conversion	104

4.1.1.2	Anaerobic Enzymatic Solubilization of Coal	104
4.1.1.3	Removal of Heteroatoms from Solubilized Coal	105
4.1.2	Results	105
4.1.2.1	Anaerobic Microbial Coal Conversion	105
4.1.2.1.1	<i>Candida</i>	106
4.1.2.1.2	Environmental Isolates	107
4.1.2.1.3	Characterization of Microbial Consortia	108
4.1.2.1.4	Growth and Product Formation by Microbial Consortia	109
4.1.2.2	Enzymatic Solubilization of Coal	111
4.1.2.2.1	Chemical Modification of Enzymes	111
4.1.2.2.2	Measurement of Activity of Hydrogenase in Organics	112
4.1.2.2.3	Model Compound Studies	113
4.1.2.2.4	Enzyme-Enhanced Coal Solubilization	113
4.1.2.3	Removal of Heteroatoms from Solubilized Coal	114
4.1.3	Future Work	115
4.2	MILD GASIFICATION PRODUCT CHARACTERIZATION	117
4.2.1	Background	117
4.2.2	Status Summary	117
4.2.3	Liquid Product Diesel Ignition Quality	117
4.2.4	Pitch Characterization	121
4.3	REFERENCES	123
5.	FOSSIL FUEL COMBUSTION TECHNOLOGY	125

5.1	TECHNICAL SUPPORT TO PETC USAID COLLABORATIVE COAL PROJECTS	125
5.1.1	Objectives	125
5.1.2	Background	125
5.1.2.1	Development of pollution control strategies for abatement of NO _x and SO _x emissions from coal-fired power plants	126
5.1.2.2	Slagging combustor development for high-ash indian coals	126
5.1.2.3	Characterization of indian coals for combustion and gasification	127
5.1.2.4	Residual life assessment and life extension of coal-fired power plants	128
5.1.2.5	Environmental and natural resource analysis of coal cycle	128
5.1.3	Status Summary	129
5.2	SUMMARY	131
	APPENDIX. ORGANIZATIONAL CHART FOR THE FOSSIL ENERGY PROGRAM	133

FOSSIL ENERGY PROGRAM SEMIANNUAL PROGRESS REPORT*
FOR APRIL 1990 THROUGH SEPTEMBER 1990

R. R. Judkins, Program Manager

ABSTRACT

This report covers progress made during the period April 1, 1990, through September 30, 1990, for research and development projects that contribute to the advancement of various fossil energy technologies. Projects on the Fossil Energy Program are supported by the DOE Office of Fossil Energy, the DOE Morgantown Energy Technology Center, the DOE Pittsburgh Energy Technology Center, the DOE Fossil Energy Clean Coal Technology Program, the DOE Office of Basic Energy Sciences, the DOE Fossil Energy Office of Petroleum Reserves, the DOE Fossil Energy Naval Petroleum and Oil Shale Reserves, and the U.S. Agency for International Development (USAID). The Fossil Energy Program organization chart is shown in the appendix.

1. SUMMARY

1.1 MATERIALS RESEARCH AND DEVELOPMENT

Research and development activities at Oak Ridge National Laboratory (ORNL) on materials for use in fossil energy systems include the fabrication and characterization of fiber-reinforced ceramic composites, development of ceramic fiber-ceramic matrix hot-gas filters, development and testing of ceramic membranes for separation of gases, microwave sintering of materials for fuel cells, development of iron aluminides, studies of environmental effects on iron aluminides, development and evaluation of advanced austenitic alloys, evaluation of materials for hot-gas filter support systems, transfer of electroslag casting technology, fundamental studies of erosion and corrosion, development of surface treatments and alloy modifications for corrosion-resistant oxide scales, materials testing and failure analysis support to coal conversion and

*Research sponsored by the U.S. Department of Energy, Office of Fossil Energy, Advanced Research and Technology Development Materials Program, under contract DE-AC05-84OR21400 with Martin Marietta Energy Systems, Inc.

utilization plants, and materials testing support to demonstration plants on the Clean Coal Program. In addition to the above research and development areas, ORNL is responsible with the DOE Field Office, Oak Ridge, for the technical management of the Fossil Energy Advanced Research and Technology Development (AR&TD) Materials Program.

In the task to develop fiber-reinforced ceramic composites, silicon carbide matrix composites were characterized for room-temperature flexure strength, room-temperature tensile strength, room-temperature fracture toughness, and high-temperature flexure strength. Measurements to determine the thermal gradient across preforms containing Nicalon fibers were made this period. Also, infiltration runs were made this period to study the effect of a constant hot-face temperature, but varying cool-face temperatures, on the characteristics of the resultant composites. Progress was also made during this period on the development of a process for the fabrication of fiber-reinforced Si_3N_4 matrix composites.

In the project to study the interfaces and mechanical properties of fiber-reinforced composites, work continued on the optimization of the strength and toughness of fiber-reinforced ceramic composites by controlling the bonding and frictional stresses at the fiber-matrix interface. The thermal stability, and oxidation and corrosion resistance of Nicalon/SiC composites were examined. Post-exposure flexure tests were performed, and optical and electron microscopy were used to analyze corrosion, glass layer formation, and compositional changes at the specimen surface and at the fiber-matrix interface. Fiber coatings are being examined to control the fiber-matrix forces in continuous fiber-reinforced ceramic composites.

In the work to develop a ceramic fiber-ceramic matrix composite that will be suitable as a high-temperature particulate filter for hot-gas cleanup systems, testing was performed during this period to investigate the corrosion of fiber-reinforced filters by sodium, potassium, and water vapor. We continued our development of ceramic membranes for the separation of gases at high temperatures. Efforts to produce the optimum membrane continued, with over 100 tubular alumina membranes produced. Permeability measurements for nitrogen, helium, and carbon dioxide were

extended to higher pressures. Work was also initiated to measure the gas permeabilities of the alumina membranes using two different gas mixtures.

In our study of the microwave sintering of materials for fuel cells, LaCrO_3 -based ceramics for the interconnect layer in solid oxide fuel cells are being evaluated. Substitution of refractory castables or firebrick for ceramic refractory fiber insulation in the microwave processing of ceramics is being pursued to reduce costs and to be responsive to environmental, health, and safety concerns.

The investigation of the performance of Fe_3Al alloys in coal gasifiers, involving product gases with relatively low oxygen activities and high sulfur activities, continued during this period. Laboratory tests were concerned with the nature and growth patterns of corrosion product scales formed in $\text{H}_2 + \text{H}_2\text{S} + \text{H}_2\text{O}$ atmospheres at 700 to 800°C. Secondary ion mass spectrography is also being used to evaluate processes controlling scale growth.

Research efforts are continuing on the evaluation of austenitic stainless steels for advanced heat recovery and hot-gas cleanup systems. In this reporting period, creep rupture testing of specimens welded with CRE 16-8-2 and alloy 556 was extended to times approaching 10,000 hours. Also, work continued on the evaluation of tubesheet designs and materials for the support of ceramic hot-gas cleanup filters.

Work on the development of iron aluminides centered on (1) the effect of chromium additions on minimizing environmental embrittlement, (2) the effect of specimen surface condition on tensile properties, (3) measurement of electrical resistivity, (4) weldability, (5) fabrication, (6) fracture testing of FA-129 alloy, and (7) technology transfer.

Our fundamental investigations on erosion and corrosion mechanisms continued with studies of the responses of metallic and oxide surfaces to deformation. These studies included: (1) the erosion behavior of 1100 Al and Fe_3Al alloys, (2) single particle impact studies to determine the effect of energy input on erosion, and (3) characterization of erosion-corrosion scales on steels. Work also continued on the study of the mechanical properties of oxide scales.

During this period, we continued our materials technical support to the Wilsonville (Alabama) Advanced Coal Liquefaction Facility.

2. MATERIALS RESEARCH AND DEVELOPMENT

R. R. Judkins

This section describes research and development activities performed for the Fossil Energy Materials Program. Work on the Fossil Energy Materials Program includes the fabrication and characterization of fiber-reinforced ceramic composites, development of ceramic fiber-ceramic matrix hot-gas filters, development and testing of ceramic membranes for separation of gases, microwave sintering of materials for fuel cells, studies of environmental effects on iron aluminides, development and evaluation of advanced austenitic alloys, evaluation of materials for hot-gas filter support systems, development of iron aluminides, fundamental studies of erosion and corrosion, and materials testing and failure analysis support to coal conversion and utilization plants.

2.1 ENVIRONMENTAL ANALYSIS AND INFORMATION SYSTEMS

Activities in environmental analysis and information systems included assistance to the DOE Office of Clean Coal Technology by initiating work on issue papers discussing environmental topics related to the Clean Coal Program, especially the effects of commercial deployment of clean coal technologies on those topic areas. Topics of the first three papers are acid deposition, global climate change, and solid waste.

ORNL is also providing assistance to the Morgantown and Pittsburgh Energy Technology Centers (METC and PETC) in reviewing and preparing documents required by the National Environmental Policy Act (NEPA) for several individual projects in the Clean Coal Program. Environmental Assessments (EA's) were prepared for two key projects for METC and PETC, respectively: Combustion Engineering's Integrated Gasification Combined Cycle project at City Water, Light and Power's Lakeside Generating Station in Springfield, Illinois, and Western Energy's Advanced Coal Conversion project at the Rosebud Mine in Rosebud County, Montana. For both projects, the EA's are expected to support documents which conclude that no significant environmental impacts will result.

2.1.1.1 Fabrication of Fiber-Reinforced Composites - D. P. Stinton,
R. A. Lowden, and T. M. Besmann

The purpose of this task is to develop a ceramic composite having higher than normal strength and toughness yet retaining the normal ceramic attributes of refractoriness and high resistance to abrasion and corrosion. Ceramic fiber-ceramic matrix composites are being fabricated by infiltrating fibrous structures with vapors that deposit on and between the fibers to form the matrix of the composites.

2.1.1.1.1 Background

Fiber composites are in the limelight as a result of exceptionally high toughness values recently achieved for glass ceramics reinforced with silicon carbide fibers. Because use of ceramics is frequently restricted by inadequate toughness, any progress toward toughening ceramics will greatly expand their potential market. However, a generic problem that must be overcome is that normal ceramic fabrication processes tend to damage fibers mechanically and chemically when the fibers are consolidated within a ceramic matrix. The purpose of this task is to form the matrix by a comparatively low-stress, low-temperature chemical vapor deposition (CVD) infiltration process that will avoid the pitfalls of conventional ceramic processing.

As reported previously, others have used CVD infiltration for fabricating ceramic composites. The vapor consolidation technique has been used to prepare fiber composites with matrices of carbon and/or such ceramics as SiC, Si₃N₄, B₄C, BN, and TiB₂.

2.1.1.1.2 Approach

Our goal is to demonstrate a rapid process for fabricating, via chemical vapor infiltration, a ceramic fiber-ceramic matrix composite consisting of materials of high interest to the fossil energy community. An initial assessment identified SiC fibers and matrices of Si₃N₄ and SiC as being promising. An infiltrating process utilizing a thermal gradient, combined with forced flow of the reactants, is being pursued.

2.1.1.3 Discussion of Current Activities

A report summarizing the characterization of SiC composites reinforced with Nicalon and Tyranno fibers was issued during this period. The conclusions from the report are summarized here. Silicon carbide matrix composites fabricated by the forced chemical vapor infiltration (CVI) process were characterized for room-temperature flexure strength, room-temperature tensile strength, room-temperature fracture toughness, and high-temperature flexure strength. Forced CVI composites fabricated at hot-face temperatures $<1200^{\circ}\text{C}$ exhibit an average flexure strength of ≈ 380 MPa and an apparent fracture toughness of $\approx 23 \text{ MPa}\cdot\text{m}^{1/2}$. Room-temperature tensile strengths obtained on a limited number of samples gave values of ≈ 230 MPa. Because these values are nearly identical to those reported by Societe Europeenne De Propulsion and DuPont for composites fabricated by the isothermal CVI process, apparently no additional fiber degradation results from the higher processing temperature (1200°C) used by the forced CVI process. Hot-face temperatures $>1200^{\circ}\text{C}$ were shown to cause significantly greater fiber degradation. Silicon carbide matrix composites reinforced with Tyranno fibers were also fabricated by the forced CVI process. The room-temperature flexure strength of the material is 50 MPa higher than Nicalon-containing composites of similar density. The 50 MPa improvement in strength is maintained to 1200°C .

Measurements to determine the thermal gradient across preforms containing 35 to 40 vol % Nicalon fibers were made this period. For nominal infiltration runs a control temperature of 1200°C is measured by an optical pyrometer sighting on the center of the graphite lid. No temperature gradient in the radial direction (across the lid) is measurable with the pyrometer despite the flow of nearly $700 \text{ cm}^3/\text{min}$ of gas through the preform. The temperature on the cool face of the composite is measured with a thermocouple that contacts the center of the preform. The thermocouple measures a bottom temperature of 750°C for a typical infiltration run (control temperature of 1200°C). The bottom temperature is reduced significantly by the reactants flowing past the tip of the thermocouple. The bottom temperature increases approximately 100°C when the flow of gases is shut off. Temperature measurements in the radial

direction on the bottom surface are not possible because the thermocouple can only be positioned in the gas path at the center of the preform. Metallographic cross sections of infiltrated composites show a variation in density across the bottom surface. There appear to be low density regions at the center near the gas inlet and at the lower, outer edge. The low density regions are most likely caused by lower temperatures, but could also be influenced by gas flow patterns.

A series of four infiltration runs was made with a 1200°C hot-face temperature and varying cool-face temperature (650, 750, 900, and 1000°C). The average densities of the four composites after infiltration were 78, 89, 65, and 43% of theoretical, respectively. The infiltration times for the four parts were 39.4, 43.8, 22.5, and 7.0 h, respectively. Higher than optimum bottom temperatures apparently cause increased SiC deposition on the bottom of the part and premature plugging of the preform. Lower than optimum bottom temperatures fail to fully densify the cool side of the preform; however, the infiltration times are approximately equal to those of optimized conditions. The densest composite, fabricated with a bottom temperature of 750°C, was cut into flexure bars to determine the density gradient through the thickness of the composite. No axial gradient in density was found. The average bulk density of 10 bars cut from each layer of the composite was 2.65 ± 0.03 , 2.63 ± 0.06 , and 2.67 ± 0.03 g/cm³ for the top, middle and bottom layers, respectively.

Progress has been made in recent months on the development of a process for the fabrication of fiber-reinforced Si₃N₄ matrix composites. Fibrous preforms were fabricated by stacking multiple layers of Nicalon plain weave cloth into a 4.4 cm diam graphite holder. Initially, fibrous preforms were infiltrated at reduced pressure; however, the results were less than satisfactory because the forced CVI equipment failed to operate properly under vacuum conditions. Several infiltrations were then conducted at atmospheric pressure, with a hot-face temperature of 1000°C and a H₂:SiCl₄ ratio of 25:1. NH₃ flows were varied methodically until NH₃ to SiCl₄ ratios were identified that permitted continuous, automatic furnace operation. Ratios of NH₃ to SiCl₄ higher than 5:1 produced copious amounts of NH₄Cl powder which plugged the exhaust and scrubber. Ratios lower than 5:1 were then investigated with the following results. A ratio

of NH_3 to SiCl_4 of 1:1 exhibited the highest density with the lowest production of NH_4Cl powder and had a total infiltration time of 33 hours. Holding the temperature, $\text{NH}_3:\text{SiCl}_4$ ratio, and $\text{H}_2:\text{SiCl}_4$ ratio constant, the total gas flow was increased such that the SiCl_4 , H_2 and NH_3 flows were 30, 750 and 30 cm^3/min , respectively. This infiltration was successful, lasting 50.1 hours, and an even higher density was achieved. An envelope of infiltration conditions has now been identified that permits continuous, automatic operation of the equipment without plugging the exhaust system. Unfortunately, these conditions continue to produce only amorphous Si_3N_4 , and further modifications will be required for the deposition of crystalline material.

Composites reinforced with Nicalon fibers are of tremendous interest for many applications. Therefore, many companies are interested in testing fiber-reinforced SiC matrix composites. Samples for room- and elevated-temperature tensile testing were fabricated, machined, and sent to North Carolina A & T State University. Samples for nondestructive evaluation have been fabricated and sent to Argonne National Laboratory and Idaho National Engineering Laboratory. Samples for interlaminar shear strength determination were fabricated and sent to E. I. DuPont de Nemours & Co. Samples for studying fracture behavior were fabricated and shipped to Argonne National Laboratory. Approximately twenty composite samples (5 by 6 mm SiC coated bars) were shipped to Idaho National Engineering Laboratory for joining studies.

2.1.2 Interfaces and Mechanical Properties of Continuous Fiber-Reinforced Ceramic Composites - R. A. Lowden, R. D. James, and K. L. More

The purpose of this task is to optimize the strength and toughness of fiber-reinforced ceramic composites by controlling the bonding and frictional stresses at the fiber-matrix interface. Methods must be developed to characterize fiber-matrix interactions and measure interfacial stresses in fiber-reinforced ceramic composite systems. Coating or pretreatment processes can then be utilized to tailor the fiber-matrix interfacial stresses within various composite systems and to optimize the strength and toughness of the composite.

2.1.2.1 Background

Production of low-cost ceramic fibers with improved strength has spurred the development of fiber-reinforced ceramic composites for high-temperature applications. The stresses at the fiber-matrix interface influence the mechanical properties of the composites. Very strong bonds result in brittle fracture because cracks propagate through both the matrix and the fiber. Extremely weak bonds between matrix and fiber fail to transfer the load from the matrix to the fiber, and the mechanical properties of the composite are thus limited by the properties of the matrix. Composites with both high strength and adequate fracture toughness can only be obtained by transferring the load to the fiber while exhibiting significant fiber pullout.

Pyrolytic carbon coating of Nicalon® fibers by Amercom and Refractory Composites resulted in improvements in mechanical properties in SiC matrices. The strength of the interfacial bond between the SiC matrix and the Nicalon fiber was reduced which resulted in increased fiber pullout and improved fracture toughness. The effect of controlling interfacial bond strengths must be investigated and understood so that fiber pretreatments or coating processes can be developed which optimize the strength and fracture toughness of various composite systems.

2.1.2.2 Approach

The goal of this project is to demonstrate that the interfacial bond between Nicalon fibers and various ceramic matrices can be measured and controlled for optimization of mechanical properties such as strength and toughness. The technical approach to be followed during this project includes four tasks: (1) develop interface characterization techniques, (2) develop bond strength measurement techniques, (3) determine candidate overcoat compositions and develop or contract for overcoating of fibers, and (4) characterize composites and correlate fiber-matrix bonding with strength and strain tolerance.

Fiber-matrix bonding and interfacial frictional stresses in this and other systems clearly influence load transfer and fiber pullout in fiber-reinforced composite systems and, thus, control the fracture toughness of the material. Techniques will be developed to investigate the interfacial

region and determine the effect of intermediate layers on the bond strength and frictional stresses and their effects on the resulting fracture toughness of the composite. Methods will be developed to measure the bond strength and interfacial frictional stress in fiber-reinforced composite systems or at least to determine the relative stresses of one fiber-matrix system as compared to another.

Once fiber-matrix interfaces can be characterized and bond strengths can be measured, methods such as fiber pretreatment or application of interfacial layers will be developed to modify and control the fiber-matrix bonds. Processes will be developed to apply the selected overcoat materials to Nicalon fiber tows or to Nicalon cloth in quantities necessary for composite fabrication. Mechanical properties of optimized composites, including room-temperature strength, high-temperature strength, and fracture toughness, will be determined and correlated with the fiber-matrix bond strengths.

2.1.2.3 Oxidation and Corrosion of Nicalon/SiC Composites

Emphasis has recently been placed on the stability of Nicalon/SiC composites at elevated temperatures in oxidizing and simulated fossil fuel environments. The development of improved fiber-reinforced ceramic composites for use in hazardous environments requires appropriate selection of external and fiber coatings. The thermal stability, and the oxidation and corrosion resistance of composites with a graphitic carbon interface layer have been examined. Composite specimens with and without an external SiC surface coating have been oxidized in air at 1273 K for periods up to 1000 h and have been exposed to a variety of combustion environments. A burner rig was constructed for simulating fossil fuel combustion environments. Postexposure room-temperature flexure tests were performed to measure the strengths of the samples after treatment, and optical and electron microscopy have been employed to analyze corrosion, glass layer formation, and compositional changes at the surface of the specimens and at the fiber-matrix interface. Correlations between exposure environment, the interface, and mechanical properties of the composites are being developed.

2.1.2.4 Experimental

Fibrous preforms were fabricated by stacking multiple layers of Nicalon plain-weave fabric rotated in a $0 \pm 30^\circ$ sequence within the cavity of a graphite holder. The layers were hand-compressed to produce a preform with a nominal loading of 40 vol % fiber and were held in place by a perforated graphite lid pinned to the holder. The cloth sizing was removed through multiple washings with acetone. The nominal size of the fibrous preforms was 75 mm in diameter and 16 mm thick.

Preforms were next precoated with a $0.3\text{-}\mu\text{m}$ layer of carbon, deposited from an argon/propylene mixture at 1375 K and 3.3 kPa pressure. The preforms were densified with SiC using a forced-flow thermal-gradient chemical vapor infiltration (FCVI) technique which has been previously described in detail elsewhere. The SiC matrix was produced by the decomposition of methyltrichlorosilane (CH_3SiCl_3 or MTS) in hydrogen using a hot-surface temperature of 1473 K and atmospheric pressure. Processing times were ≈ 40 h and the infiltrated composite samples had a nominal density of 2.6 g/cm^3 , or approximately 85 to 90% of theoretical density.

Bars were cut from the samples parallel to the 0° orientation of the top layer of cloth using a diamond saw, and tensile and compression surfaces were ground parallel to the long axis of the specimen. The average dimensions of the test bars from the composite samples were $3 \times 4 \times 50\text{ mm}$ and all specimens were measured and weighed to determine densities. A portion of the specimens were coated with a $40\text{-}\mu\text{m}$ SiC layer deposited from MTS in hydrogen at 1473 K and 3.3 kPa.

Composite specimens were oxidized in static air at 1273 K for 100, 500, and 1000 h. Flexure bars with and without SiC surface coatings were placed in the cavity of an atmospheric box furnace and heated to temperature at 300°C/h . Once the furnace achieved equilibrium, the final temperature was measured and set using a hand-held optical pyrometer, and maintained using a thermocouple-controlled programmer. At the specified time, the furnace was shut off and allowed to cool unassisted.

A burner rig furnace was employed to examine the oxidation and corrosion of the Nicalon/SiC composite specimens in simulated combustion environments (Fig. 2.1.2-1). Constant temperature was maintained by a resistively heated clam shell furnace, and an aluminum oxide tube was used as a combustion chamber. Concentric aluminum oxide tubes carried natural

Fig. 2.1.2-1. Schematic of the burner rig furnace.

gas, air, and other gases into the hot zone where they mixed and combusted. A platinum wire mesh affixed to the outlet of the burner tube ensured ignition of the gases. Mass flow controllers were used to regulate gas flow, and total gas flow was maintained at a nominal 5.5 L/min in all experiments.

Flexure bars were arranged laterally on an aluminum oxide base placed approximately 25 cm from the burner outlet. The furnace was heated to 1273 K and allowed to equilibrate. Combustion gases were then introduced to the system and conditions were held constant for 100 h; then, reactant flows were terminated and the furnace allowed to cool. Building-supplied air and natural gas were used, and a fuel-to-air ratio of 0:1 was maintained in all tests. The calculated fractions of the combustion products in the burner rig furnace are given in Table 2.1.2-1.

Sulfur-containing atmospheres, which can result from the burning of fossil fuels such as coal, were simulated by adding hydrogen disulfide gas, H_2S , to the combustion gas mixture. A sulfur content of 1% was selected from various sources and was accomplished by adding 50 cm^3/min H_2S to the system. The predicted species produced by the addition of the sulfur-containing gas to the burning of natural gas in air is also given in Table 2.1.2-1.

Sodium carbonate, Na_2CO_3 , was used as the source of sodium in the experiments. An aluminum oxide boat was filled with Na_2CO_3 and sintered at 1173 K for 24 h. The sintered sample was heated to 1173 K in the burner rig upstream from the composite specimens. Na_2CO_3 was introduced into the

Table 2.1.2-1 Calculated composition of combustion atmospheres

Species	Gas/air	+1% H_2S (vol %)	+ Na_2CO_3
N_2	71.2	71.0	71.2
H_2O	15.7	14.7	15.7
CO_2	9.3	9.3	9.3
O_2	1.9	1.4	1.9
NO_x	1.8	2.5	1.8
H_2SO_3		1.0	
Na_2O			≈80 ppm Na

combustion chamber by passing a portion of the combustion air over the boat. A sodium carbonate flow of $0.24 \text{ cm}^3/\text{min}$ was calculated from the weight change of the sintered sample, producing a sodium concentration of $\approx 80 \text{ ppm}$ in the gas mixture (Table 2.1.2-1).

2.1.2.5 Characterization

Room-temperature flexure strengths for the treated composites were measured in four-point bending. A support span of 40 mm, a loading span of 20 mm, and a crosshead speed of 0.508 mm/min were used and all specimens were loaded perpendicular to the layers of cloth. Load-displacement curves were recorded to examine the fracture process and were used to determine the loads for ultimate strength calculations.

The fracture surfaces of the specimens were examined using a Hitachi S-800 scanning electron microscope (SEM). Specimens that did not completely break during flexure testing were broken by hand so that the fracture surfaces could be examined. Polished specimen cross sections were prepared using standard metallographic techniques and were examined using optical microscopy. Detailed characterization of the effects of environmental exposure on the interfacial regions of the composites was also performed employing transmission electron microscopy (TEM).

2.1.2.6 Oxidation

The effects of oxidation on the unprotected composite specimens with a carbon interlayer were found to be progressive (Fig. 2.1.2-2). A degradation in strength was observed after 100 h of exposure; however, the composites exhibited extensive fiber pullout and enormous strain-to-failure. Longer exposure times produced embrittlement of the composites. TEM analysis of the fiber-matrix interface in the brittle specimens revealed that an amorphous silica layer replaced the carbon interlayer (Fig. 2.1.2-3). The silica layer strongly bonds the components together, thus resulting in a lack of fiber debonding and sliding, i.e., brittle fracture.

In contrast, the carbon interlayer remained intact in the samples with a $\approx 40\text{-}\mu\text{m}$ -thick SiC protective coating even after 1000 h of exposure (Fig. 2.1.2-4). Room-temperature flexure strengths in excess of 300 MPa were recorded. A slight discoloration of the surfaces of the flexure bars

[time at 1273 K indicated on curves]

Fig. 2.1.1.2-2. The effects of oxidation on the unprotected samples were progressive. Time at 1273 K indicated on curves.

AN AMORPHOUS SILICA LAYER REPLACES THE CARBON INTERLAYER IN UNCOATED OXIDIZED SAMPLES

UNCOATED 1000 HOURS

SEAL COATED 1000 HOURS

Fig. 2.1.2-3. TEM micrographs of the interface in Nicalon/Sic composites:
(a) as fabricated showing graphitic carbon coating, and (b) the silica that
forms after 1000 h of oxidation.

Fig. 2.1.2-4. The effects of oxidation on the flexure strength of Nicalon/Sic composites with a carbon interface coating.

indicated that the samples had oxidized; however, no weight change could be measured. These results demonstrated that the long-term, elevated-temperature stability of these composites may require the application of external protective layers.

2.1.2.7 Corrosion

Exposure to the combustion products of natural gas and air at 1273 K accelerated the embrittlement of the composites. Similar to the oxidation results, the properties of the composites with a SiC outer layer were unchanged. However, the uncoated specimens were brittle with low strength after a 100-h exposure (Fig. 2.1.2-5). TEM analysis again showed the carbon interlayer was removed and oxidation of the fibers and matrix resulted in the formation of an amorphous silica layer at the interface. The presence of water vapor increases the oxidation rate of SiC, thus explaining the enhanced embrittlement in the combustion environment.

A thick glassy layer was formed on the surface of the specimens tested in the sodium-containing environment. The glass coating resulted from the corrosion of the protective SiC coating, and of the matrix and fibers for the unprotected specimens. The carbon interlayer remained intact in seal coated samples and flexure strengths were only slightly decreased (Fig. 2.1.2-5). Uncoated flexure bars were brittle, and no evidence of the carbon interlayer could be found throughout the samples. The initiation of fiber and matrix consumption was also observed in the unprotected specimens. Areas near the surface of the bars were extensively attacked during exposure. It is expected that long-term exposure to sodium would cause a degradation of even the coated samples as protective layer and finally the composite would be consumed and transformed into a low melting temperature, low viscosity soda glass corrosion product.

Both protected and unprotected composites were affected by the exposure to sulfur-containing environments. Specimens exhibited flexure strengths lower than materials treated in all other atmospheres (Fig. 2.1.2-5). The presence of sulfur has been found to accelerate oxidation of SiC; however, oxidation does not appear to be the mechanism in these experiments since the carbon layer remained unchanged in the protected specimens. Detailed characterization of the specimens including

100 h at 1273 K

Fig. 2.1.2-5. The effects of 100-h exposure to various atmospheres at 1273 K on the flexure strength of Nicalon/SiC composites.

microprobe analysis of the presence of sulfur in the fibers, matrix, and interlayer areas will be completed to further examine these results.

2.1.2.8 Interfacial Shear Stress Measurements

Fiber coatings are being examined to control the fiber-matrix forces in continuous fiber-reinforced ceramic composites. Interfacial shear stresses play a significant role in determining the mechanical properties of a fiber-reinforced composite; thus, the forces at the fiber-matrix interface must be understood and controlled to produce materials with specific combinations of strength and toughness. It has been demonstrated that interfacial forces are influenced by the properties and thickness of the interlayer. Interfacial shear stress, matrix cracking, work of fracture, and ultimate strength for Nicalon/SiC composites have been modified by varying the thickness of a graphitic carbon coating.

Samples with carbon interlayer thicknesses of 0.1 to 1 μm have been evaluated; however, the interfacial shear stress measurements were made using a standard hardness indenter. Debonding and frictional stresses at the fiber-matrix interface as well as the residual stresses due to the thermal expansion mismatch of the fibers and matrix cannot be determined using this technique; thus, other methods are being explored. The interfacial shear stress for the samples with varying carbon layer thicknesses was analyzed using the Nanoindenter in the High Temperature Materials Laboratory at ORNL. The results for composites with thicker carbon layers ($>0.1 \mu\text{m}$) were similar to the previously measured values, as shown in the comparison in Fig. 2.1.2-6. Due to its low load capability, the Nanoindenter was unable to debond and slide the fibers with thinner coatings. The Nanoindenter data is also being used to determine the magnitude of the thermal expansion mismatch induced residual stresses at the interface.

Fig. 2.1.2-6. The relationship between carbon coating thickness and interfacial shear stress in Nicalon/SiC composites.

The implementation of the indentation techniques requires long, continuous fibers embedded in a matrix, and it is assumed that the thickness of the specimens is much greater than the sliding length of the fiber. The sliding length issue and the effects of Poisson expansion of the fibers during compressive loading have been the subjects of numerous debates. It is recognized that a "pure pushout" test would be more useful and accurate in the measurement of interfacial forces. Therefore, the composite specimens with varying carbon interlayer thicknesses have also been provided to Lance Snead, a doctoral candidate at Rensselaer Polytechnic Institute, who also is employed as a graduate student in the Structural Materials Group in the Metals and Ceramics Division. The composite specimens have been carefully thinned using techniques similar to those used to prepare samples for TEM analysis. Fibers are being pushed out of the thin specimens using the Nanoindentor. The specimens are then inverted, and the fibers pushed back into the specimen in the opposite direction. This technique permits the measurement of debonding and interfacial shear stresses as well as the determination of frictional sliding forces as the fiber is pushed in the reverse direction. The measurements will be compared to the values determined employing a standard hardness indenter and the Nanoindentor.

2.1.2.9 Alternate Coatings

The poor oxidation resistance of carbon has led to the examination of alternate coating materials or concepts for controlling the force at the fiber-matrix interface in ceramic-ceramic composites. Many factors must be considered in the selection of materials for interlayers in any high-temperature composite system. Chemical compatibility with the fibers and matrix, elevated-temperature stability, and oxidation resistance are obvious requirements for an interface coating; however, the mechanical and physical properties of the coating also play an important role in determining interfacial bonding and shear stresses.

The theoretical aspects of thin films at the interface in whisker- and fiber-reinforced ceramic composites and their effects on the stresses due to thermal expansion mismatches have been examined by others.¹ A reduction in thermomechanical stress is suggested only when a low modulus interfacial coating is present. For many composites, the matrix has a higher thermal

expansion than the fiber; thus, upon cooling from processing temperatures, a clamping of the fibers occurs. An interlayer must alter the compressive stresses at the interface to permit debonding and produce low interfacial shear stress. A coating that is able to deform (i.e., low modulus) can act as a buffer layer and accommodate a portion of the residual clamping stress of the matrix, thus controlling interfacial shear and frictional forces.

Few materials possess all of the properties essential for the ideal interface layer. A graphitic carbon coating has proven to perform well in numerous ceramic composite systems including fiber-reinforced glasses and ceramics and SiC whisker-toughened alumina. Carbon oxidizes at temperatures <700 K; thus, other materials with properties similar to carbon but possessing improved oxidation resistance are being examined. Boron nitride coatings with structures and properties comparable to graphite can be produced by chemical vapor deposition (CVD); and, in addition, BN offers a distinct improvement in oxidation resistance. However, with the exception of a small sample of CVD coated fabric,* all previous experiments with BN-coated Nicalon were disappointing. Attempts to deposit polycrystalline BN layers on the fibers using CVD techniques resulted in extensive damage to the fibers, and amorphous deposits produced at low temperatures decomposed at room temperature.

However, favorable results were obtained from the limited supply of CVD-coated fabric and there have been reports of improved long-term oxidation resistance for BN-coated fibers in analogous composite systems. This prompted the re-evaluation of BN as an interface layer. Previous efforts were reviewed and experimental conditions for the deposition of crystalline BN were determined. BN coatings were deposited on individual cloth layers as well as complete preforms. Deposition conditions were varied to alter the composition and the thickness of the interlayer. Although the strengths of the coated fibers were not measured, the fibers remained flexible and intact after deposition. Composites were fabricated from the coated fabric and the mechanical properties and the oxidation resistance of these materials are to be examined and compared to the results for composites with carbon interlayers.

*Produced by Comurhex, CVD Department, Pierrolette, France.

CVD is one of numerous methods that have been employed for the deposition of thin layers on the surface of fibers. Sol-gel techniques have also proven useful for producing coatings on fibers, especially for oxide coating compositions. Nicalon fabric samples were coated with oxide layers by Dr. Jay Lane at Westinghouse Science and Technology Center, Pittsburgh, PA. Eight oxide compositions of two thicknesses were applied to Nicalon plain-weave cloth using sol-gel techniques. The coatings included alumina, mullite, calcium-doped cordierite, alumina-magnesia-yttria, titania, zircon, zirconia, and yttrium-doped zirconia. The coated fabric is being incorporated into composites, and the effectiveness of the oxide interlayers is to be examined.

2.1.3 Ceramic Fiber-Ceramic Matrix Hot-Gas Filters - D. P. Stinton and L. R. Riester

The purpose of this project is to develop a ceramic fiber-ceramic matrix composite that will be suitable as a high-temperature particulate filter for use in hot-gas cleanup systems. The goal is to produce a composite that has the requisite strength and toughness, but which also has sufficient porosity to be permeable to the gas stream and the size and distribution of porosity to be an effective filter. A practical process will be developed for fabricating porous ceramic fiber-ceramic matrix filter materials in both disk and cylindrical shapes.

2.1.3.1 Background

The Fossil Energy AR&TD Materials Program has been developing composite materials with improved properties for use in fossil energy systems. One of the materials is a ceramic fiber-ceramic matrix composite made by chemical vapor deposition. In this process, a ceramic material (SiC) is deposited on the fibers of a fibrous preform bonding them together, and partially filling the space between the fibers. This process will be modified to produce ceramic fiber filter materials for use in hot-gas cleanup systems. Fibrous preforms containing appropriate volume loading will be partially infiltrated with a ceramic matrix to provide sufficient strength, toughness, and porosity to provide adequate gas flow through the porous fiber medium. Such a composite provides excellent

filter efficiency and cleanability and should have the mechanical properties required to tolerate the cyclic stresses imposed in service.

2.1.3.2 Approach

Fibrous preforms are fabricated by several techniques to assure optimization of filter efficiency and cleanability. Fibrous preforms are produced by sandwiching a layer of felt between two layers of loosely woven cloth. The felt functions as the filter medium and after infiltration the cloth provides mechanical strength. It is desirable that 100% of the particulates be filtered at the sample surface, since particulates that penetrate the filter medium would not likely be removed during cleaning. Infiltration of the preform should firmly bond the cloth to the filter medium and stabilize the felt (bond individual fibers together) to prevent fiber loss during pressure-pulse cleaning. Filter designs investigated include stand-alone felt, cloth layers applied to the inner surface, and outer surface, or both the inner and outer surfaces of the preform. The relationships between filter efficiency, cleanability, strength and toughness, chemical compatibility (with the hot-gas stream), preform characteristics (fiber, volume loading of fiber, and preform fabrication technique), and infiltration conditions (temperature, gas compositions, and flow rates) will be established to optimize the properties of the filter materials.

2.1.3.3 Discussion of Current Activities

Corrosion by sodium, potassium, and water vapor has been identified as a potentially serious problem for fiber-reinforced hot-gas filters overcoated with SiC. Normally, SiC would oxidize at high temperatures to form an SiO₂ layer which would prevent further oxidation. However, sodium, which is present in high-temperature combustion atmospheres, reacts with the SiO₂ layer to form a glass that is no longer protective. To make matters worse, water vapor present in the combustion atmosphere catalyzes the reaction of SiC to form SiO₂. Previous testing of fiber-reinforced filters overcoated with chemically vapor deposited SiC showed the material to be susceptible to corrosion by ≈ 200 ppm of sodium at 1000°C. The concentration of sodium for these tests was considerably higher than

expected in actual systems. Therefore, further testing was performed this period under more realistic conditions.

Samples of sintered alpha-SiC and chemically vapor deposited SiC were exposed to a combustion atmosphere containing 5 to 10 ppm of sodium at 1000°C for 100 h. Ceramographic cross-sections of the sintered alpha SiC and chemically vapor deposited SiC indicated that a glass layer of about 5 μm was formed on their surfaces. The glass layer did not melt and flow off the samples as in the previous tests at high sodium concentrations (200 ppm). The rate of corrosion of the chemically vapor deposited SiC appeared no worse than the sintered alpha SiC. To determine the effect of the sodium on the oxidation rate of the SiC, this test was repeated without sodium present. Under these conditions the oxide layer thickness was reduced from 5 to 1 μm . Chemically vapor deposited SiC again oxidized at a rate equal to that of sintered alpha SiC. Additional tests with sodium present are planned for longer times to determine if the glass layer protects the SiC from further oxidation and corrosion.

Also included in the 100 h test with sodium were SiC matrix composites reinforced with Nicalon fibers (similar to fiber reinforced filters except much denser). These composites had been overcoated with about 30 μm of SiC to protect the material from oxidation. The flexure strength of this material was maintained despite the presence of the glass surface layer. Apparently, the SiC layer had protected the Nicalon fibers for the duration of this test. Longer duration tests will be required to determine how long the Nicalon fibers will be protected by the SiC layer.

Materials more resistant to sodium will need to be developed that can be used in place of SiC or as a protective coating for SiC in the most severe applications. One material that has exhibited better resistance to sodium corrosion than SiC is zirconia. Pure ZrO_2 is a complex material that exists in several different crystal structures. The low temperature form undergoes a phase transformation from monoclinic to tetragonal at 1000°C which involves a large volume contraction that makes the use of pure zirconia impractical as a bulk material or a coating. Addition of Ca, Mg, Y, or Ce to form a cubic solid solution (stabilized zirconia) that is stable from room temperature to >1500°C results in a valuable structural material. Unfortunately, coatings will not normally adhere to a substrate

the coefficient of thermal expansion (CTE) of stabilized zirconia is about 13×10^{-6} which is considerably higher than that of SiC (5.5×10^{-6}). Zirconium carbide, however, has a CTE very similar to that of SiC (about $7.0 \times 10^{-6}/K$) and should adhere quite well to a SiC substrate. Conversion of several microns of the ZrC to ZrO_2 to form a protective oxide layer will be attempted as one method to reduce the effects of sodium corrosion on SiC.

Following a review of the literature, zirconium carbide was successfully deposited onto SiC by chlorinating zirconium metal at $450^\circ C$ and reacting those vapors with methane and hydrogen at $1200^\circ C$. Controlled oxidation of the ZrC layer at about $800^\circ C$ produced a thin layer identified by x-ray diffraction as monoclinic ZrO_2 that did spall away from the underlying ZrC. Modifications to the deposition process will be required to incorporate Ca, Mg, Y, or Ce into the ZrC so that controlled oxidation will produce stabilized zirconia. If the thermal expansion of the stabilized zirconia is too great to adhere to ZrC, attempts will be made to deposit partially stabilized zirconia (a mixture of cubic zirconia and tetragonal zirconia; $CTE = 10 \times 10^{-6}$) that should adhere to ZrC.

2.1.4 Gas Separations Using Inorganic Membranes - B. Z. Egan,^{*}
S. P. N. Singh,^{*} D. E. Fain,[†] G. E. Roettger,[†] and D. E. White[†]

The objective of this project is to develop, fabricate and evaluate inorganic membranes for separating gases at high temperatures and pressures and/or in hostile process environments encountered in fossil energy conversion processes such as coal gasification. Major tasks presently being investigated include (1) fabrication and physical characterization of membranes at the Oak Ridge K-25 Site; and (2) evaluation of the separations capability of the fabricated membranes in terms of permeabilities and fluxes of gases using a testing apparatus at Oak Ridge National Laboratory (ORNL).

^{*}Chemical Technology Division, Martin Marietta Energy Systems, Inc., Oak Ridge, Tenn.

[†]Technical Division, K-25 Site, Martin Marietta Energy Systems, Inc., Oak Ridge, Tenn.

2.1.4.1 Background

Synthesis gas produced in coal gasification processes contains hydrogen, along with several other gases, including carbon monoxide, nitrogen, water, carbon dioxide, hydrogen sulfide, and small amounts of other gases. Inorganic membranes could potentially be used to separate these gases under gasifier exit gas conditions, and thereby significantly improve process efficiency and economics. The separation and recovery of hydrogen is of particular interest.

Polymeric membranes have been used on a commercial scale to separate hydrogen from various gases. These membranes have limited thermal stability and are susceptible to abrasion and chemical attack. Consequently, they cannot be utilized in many separation processes.

Until recently, inorganic membranes have been used primarily for microfiltration and ultrafiltration. However, gas permeabilities have been measured for many porous metals, glasses, and ceramics. These materials are stable to much higher temperatures than polymeric membranes, and the limitation is usually set by the seals and module materials and not the membrane itself.

Several porous inorganic materials that could be used as membranes are commercially available, but the minimum pore diameter is in the range of 30 to 40 Å. While some gas separations can be achieved with these materials, it is generally accepted that smaller pore diameters or other membrane modifications will be needed for efficient gas separations.

2.1.4.2 Approach

Several tasks have already been completed as part of this program. The literature on inorganic membrane R&D to separate gases was compiled and summarized in a report.² The performance targets for a membrane separation process applied to a coal gasification process were determined, based on the operating temperatures, pressures and gas flux requirements. Potential membrane materials were selected, based on thermal and chemical stability, availability and cost of raw materials, and effects on gas transport mechanisms. Alumina was chosen as the best membrane material for the initial studies.

Present work is directed toward fabricating improved membranes and testing them on a laboratory scale for separating gases of interest. The

technical approach is to develop and fabricate membranes with small pores (less than 20 Å) and a narrow pore size distribution to take advantage of gas transport mechanisms other than, or in addition to, simple Knudsen diffusion, to provide increased gas selectivity. Lab-scale tests are conducted on the best membranes to measure the permeabilities of components of synthesis gas. Finally, the membrane will be tested with a simulated coal gasification mixture.

2.1.4.3 Discussion of Current Activities

Efforts to produce the optimum membrane are continuing. Over 100 tubular alumina membranes, with a diameter of about 0.9 cm, have been fabricated. The average pore radius of the membranes was reduced to less than 10 Å. Some of the membranes had essentially no pores with a radius greater than 20 Å. Efforts to prepare membranes with still smaller pores are continuing.

Initial gas permeability measurements using these membranes were reported previously. The permeabilities of the membranes were measured at room temperature using helium, nitrogen, and carbon dioxide. In addition, the permeabilities of one set of membranes were also measured using air and sulfur hexafluoride. The permeability of the gases did not vary appreciably with pressure for the gases at the relatively low pressure ranges that were tested.

During this reporting period, permeability measurements for nitrogen, helium, and carbon dioxide have been extended to higher pressures using the ORNL test system on alumina membrane samples obtained from the K-25 Site. Measurements were made at room temperature in the pressure range of 15 to 150 psi (Fig. 2.1.4-1). Nitrogen and helium permeabilities of a second membrane sample were measured up to a feed gas pressure of 589 psi (Fig. 2.1.4-2).

In general, the order of permeability was $\text{He} > \text{N}_2 > \text{CO}_2$; the relative gas permeabilities correlate qualitatively with a Knudsen flow mechanism. However, it is apparent that other gas transport mechanisms play a role, particularly in the case of carbon dioxide. The enhanced permeability of carbon dioxide, probably due to membrane interaction, reduces the helium/carbon dioxide separation factor.

Fig. 2.1.4-1. Gas permeabilities of a fabricated alumina membrane at room temperature (Mean Pore Radius, 18Å).

Fig. 2.1.4-2. Helium and nitrogen permeabilities of a fabricated alumina membrane at high pressure.

The helium/nitrogen separation factor is also reduced somewhat as the pressure increases because the nitrogen permeability increases more rapidly with pressure. This behavior also indicates that gas transport mechanisms other than Knudsen flow are involved. These data reinforce the need to develop membranes with smaller pores to take advantage of other gas transport mechanisms, such as molecular screening, to improve the separation factors for the gases of interest.

Work has been initiated to measure the gas permeabilities of our fabricated alumina membranes using two different gas mixtures. The first membranes tested were prepared some time ago and have relatively large pores. The membrane assembly contained an epoxy seal, so initial tests were done at room temperature and at relatively low pressures. One of the gas mixtures contained hydrogen, carbon monoxide, carbon dioxide, and methane; the second mixture contained these gases, along with nitrogen. The feed, raffinate, and permeate gas streams were analyzed by gas chromatography. The pressure on the feed side of the membrane ranged from 65 to 75 psig; the permeate pressure ranged from about 23 to 29 psig. The relative flow rates of the raffinate and permeate gases were varied. As expected, there was some hydrogen enrichment in the permeate. Quantitative analysis has not been completed. However, it was estimated that when the gas mixture in the feed stream contained 35% hydrogen, the permeate concentration reached about 45%. A mixture containing about 20% hydrogen gave a permeate containing about 25% hydrogen. Further tests are planned. Present efforts are directed toward developing better seals for making gas permeability measurements at higher temperatures, and we are continuing our effort to develop membranes with still smaller pores.

2.1.5 Microwave Sintering of Materials for Fuel Cells - M. A. Janney and H. D. Kimrey

Microwave processing of LaCrO_3 -based ceramics for the interconnect layer in the solid oxide fuel cell is being evaluated.

2.1.5.1 Sintering of LaCrO_3 Materials

Figure 2.1.5-1 is a sintering curve for the composition $(\text{La}_{0.79}\text{Ca}_{0.2})(\text{Cr}_{0.9}\text{Co}_{0.1})\text{O}_3$ which compares the sintering behavior for conventional and microwave sintering. Samples were heated at $10^\circ\text{C}/\text{min}$ to the sintering temperature and held for 1 h at temperature. The sintering response of the

Fig. 2.1.5-1. Microwave sintering of $(\text{La}_{0.79}\text{Ca}_{0.2})(\text{Cr}_{0.9}\text{Co}_{0.1})\text{O}_3$ was somewhat more rapid than conventional sintering.

two methods was similar, with the sintering of the microwave-fired samples being perhaps slightly better.

The microstructure of the fired $(\text{La}_{0.79}\text{Ca}_{0.2})(\text{Cr}_{0.9}\text{Co}_{0.1})\text{O}_3$ consisted of a major phase of primary idiomorphic grains (primarily rectangular prisms) of LaCrO_3 solid solution surrounded by an intergranular liquid phase, together with $\approx 6\%$ porosity (see Fig. 2.1.5-2). The primary grains contained mainly La and Cr, as one would expect from a LaCrO_3 composition, with a small amount of Ca and Co. However, there was an interesting feature to these grains. Most of them contained a "precipitate," i.e., the center of the grains was rich in La and poor in Ca (see Table 2.1.5-1). The intergranular liquid phase was essentially a cobalt oxide melt with 5 to 10 cation % Cr, and trace amounts of La and Ca. In the samples fired at 1300°C in the microwave furnace, two different liquid phase compositions were found, presumably because the temperature achieved during sintering

ORNL-PHOTO 3348-90

Fig. 2.1.5-2. The $(\text{La}_{0.79}\text{Ca}_{0.2})(\text{Cr}_{0.9}\text{Co}_{0.1})\text{O}_3$ microstructure consisted of "cored" primary grains with an intergranular liquid phase high in Co and Cr, and depleted in La and Ca.

Table 2.1.5-1. Compositional differences among phases processed under different conditions in the lanthanum chromite $[(La_{0.79}Ca_{0.2})(Cr_{0.9}Co_{0.1})O_3]$ system

Feature	Time (h)	Temperature (°C)	Sample	Cation concentration (%)			
				La ^a	Ca	Cr	Co
Matrix Composition							
MW	1	1300	LMW90002	37.55	8.72	49.53	4.21
MW	48	1400	LMW90010	40.22	9.49	46.30	3.99
Conventional	1	1400	LC90003	38.5	9.4	47.5	4.5
Conventional	1	1500	LC90005	38.9	9.2	47.7	4.2
Conventional	48	1400	LC90008	38.35	10.02	47.89	3.73
Precipitate Composition							
MW	1	1300	LMW90002	41.07	5.22	49.17	4.54
MW	48	1400	LMW90010	45.80	4.31	47.25	2.64
Conventional	1	1400	LC90003	43.7	5.2	45.7	5.4
Conventional	1	1500	LC90005	43.8	4.4	48.0	3.7
Conventional	48	1400	LC90008	43.94	5.48	46.68	3.89
Boundary Region Composition							
MW	48	1400	LMW90010	39.02	11.08	45.18	4.72
Conventional	48	1400	LC90008	36.45	12.86	46.68	4.01
Liquid Phase Composition							
MW, 1 h	1	1300	LMW90002				
			Liquid #1	9.70	2.62	46.27	41.41
			Liquid #2	2.86	0.73	7.41	89.01
MW, 48 h	48	1400	LMW90010				
Conventional	1	1400	LC90003	5.5	1.5	9.8	83.3
Conventional	1	1500	LC90005	6.7	1.8	11.3	80.2
Conventional	48	1400	LC90008	0.68	1.00	4.40	93.90

^aCation at. %, where La + Ca + Cr + Co = 100%.

was not high enough to homogenize the microstructure. To further investigate the process of homogenization, long-term annealing studies were conducted under both conventional and microwave firing conditions.

Samples annealed at 1400°C for 48 h showed significant differences in their microstructures. The grain size of the microwave-fired sample was much larger than that of the conventionally fired sample (see Fig. 2.1.5-3). In addition, the morphology of the grains was different. The conventionally fired sample retained much of the blocky, idiomorphic grain structure that had been observed earlier in the short-time sintering samples. The microwave-fired sample exhibited a grain morphology closer to a "soap bubble" structure, with solution rims surrounding many of the grains; no entry for "Liquid Phase Composition" is made in Table 2.1.5-1 for the 48-h microwave-fired sample because no pockets of liquid phase large enough to be analyzed could be found. These results suggest that, while long firing times are required to achieve homogeneity in this particular system, the kinetics of homogenization are faster for microwave than for conventional firing. This result is somewhat surprising given the similarity in the sintering densification curves for the two systems.

2.1.5.2 Evaluation of Substitute Insulation Materials for Microwave Processing

Substitution of refractory castables or firebrick for ceramic refractory fiber (CRF) insulation in the microwave processing of ceramics is being pursued. At least two reasons are driving this substitution study. First, the cost of the fiber refractories is at least 100 times higher than the cost of conventional castable or insulating firebrick; given the high probability of unexpected chemical interactions, runaway heating to meltdown, etc., the lifetime of a particular refractory insulator in the microwave furnace is limited and replacement is expensive. Second, in response to the increasing emphasis on environmental, safety, and health issues at the DOE laboratories, concerns over the safety of CRF have been raised. In order to make sure that our microwave processing efforts are not shut down by a possible safety decree, it is important that we have a backup system for insulating our experiments.

YP11523

Fig. 2.1.5-3. The microstructures of the 48-h annealed samples were quite different for the microwave (a) and the conventional (b) firings. The grain size in the microwave-fired sample was about twice the size of that for the conventionally fired sample and the idiomorphic grain shape was largely destroyed.

We have evaluated a number of commercial refractory materials for their heating behavior in a microwave furnace. We have discovered that the heating behavior of these materials depends critically on both their chemical composition and on their thermal history, which determines the phases that are present. These materials belong to the general class of castable refractories. As such, they consist of a refractory filler material, typically calcined clay or alumina, and a hydraulically setting cement phase, either portland cement (for applications up to $\approx 1000^{\circ}\text{C}$) or calcium aluminate cement (for applications up to $\approx 1700^{\circ}\text{C}$). There are numerous phase changes that occur during the casting and firing of these materials, including hydration (on addition of water to the dry powder), dehydration (during drying and low-temperature firing), and chemical homogenization and recrystallization (during high firing). The dielectric properties of the materials at each stage of processing will be different because of the differences in the phase composition. Figure 2.1.5-4 shows the heating curves for a number of materials. The heating curves were determined using a sample size of ≈ 150 mL, in a 700-W, 2.45-GHz microwave furnace. Figure 2.1.5-4(a) shows that the heating of both K3300 and K1600 castables* was small after heat treatment at 800°C prior to testing; however, when K3300 was further heat treated at 1425°C , its susceptibility to heating was increased dramatically, most likely by the formation of a new, high loss phase that was formed during the 1425°C anneal. Likewise, in Fig. 4(b) we observe that the K1600 refractory was very susceptible to heating directly after drying, but was much less susceptible after heating at 800°C , presumably because of the elimination of the chemically bound water of hydration. Our evaluation of these and other refractories is continuing and will include a determination of their dielectric properties as a function of their phase composition.

*Thermal Ceramics, Inc., Augusta, Ga. The number designation indicates the upper use temperature of the refractory in degrees Fahrenheit.

a

b

Fig. 2.1.5-4. The heating response of the castable refractories depended on their composition and on their thermal histories: (a) behavior of K1600 and K3300 refractories after heat treatment at 800°C and 1425°C; (b) behavior of K1600 refractory after drying at 100°C and after firing to 800°C.

2.2 NEW ALLOYS

2.2.1 Environmental Effects on Iron Aluminides- J. H. DeVan

Alloys based on the long-range-ordered system Fe_3Al are under development at Oak Ridge National Laboratory in support of coal conversion and combustion materials requirements. Of particular interest is the performance of these alloys in coal gasifiers involving product gases with relatively low oxygen activities (10^{-20} atm) and high sulfur activities (10^{-8} atm). Using H_2S - H_2 - H_2O gas mixtures, several experimental iron-aluminum alloys have been tested to assess the effects of aluminum concentration on corrosion behavior at 700 to 800°C in a simulated gasifier environment. Thermogravimetric analyses, together with metallographic and chemical analyses of the corrosion product scales, are performed to determine the role of respective metallic elements on oxidation and sulfidation processes. Additionally, the corrosion resistance of Fe_3Al alloys is being evaluated by exposures at 600 to 900°C in the gas-cooler section of an operating gasifier in the United Kingdom.

2.2.1.1 Discussion of Current Activities

As reported earlier,³ we provided an Fe_3Al alloy containing 2% Cr to the Coal Research Establishment (CRE) of the British Coal Corporation for testing in a 12-ton/day nonpressurized gasifier at Stoke Orchard, Gloucester. The corrosion behavior of the alloy was in good agreement with that seen in the laboratory, with negligible attack (<40 mm) occurring even at the highest exposure temperature. The gasifier used for this evaluation has since been "mothballed"; however, testing of the alloy will be continued in association with a topping cycle development program being conducted at CRE. The latter concept couples a gas turbine with a pressurized coal gasifier and also incorporates either a circulating fluid bed or pressurized fluidized-bed combustor (PFBC) which will operate on char from the gasifier. To examine several issues concerning gasification aspects of the cycle, CRE has modified an existing PFBC system at Stoke Orchard to permit operation as an air-blown pressurized gasifier. A series of alloys will be exposed to product gas as it exits the gasifier prior to entering the gas cleanup system. The specimens are required to be in the

form of rings, 36 mm OD $\times$ 26 mm ID $\times$ 10 to 20-mm-long, and will be supported on a common mandrel. Two Fe₃Al-based alloys, one containing 2% Cr (FAS) and the other 5% Cr (FA-129), were fabricated to the required dimensions and supplied to CRE in June. The scheduled startup date for these tests is September 1990.

Laboratory tests of iron aluminide during this reporting period were concerned with the nature and growth patterns of corrosion product scales formed in H₂S-H₂-H₂O atmospheres at 700 to 800°C. As reported previously,³ the following general features have been observed in tests to date. In common with tests in air at equivalent times and temperatures, scales formed on binary alloys containing iron plus 28 to 40% aluminum have been composed entirely of aluminum oxide with no apparent sulfides or iron-containing oxides. Thus the rate of scale growth and exfoliation for binary alloys in our relatively reducing, sulfur-containing test environment has been acceptably low. Nevertheless, the rate is notably faster than in air. If >2% chromium is added as an alloying element to alloys containing 28% aluminum, the morphology and growth kinetics of the scale changes, as aluminum, chromium, and iron sulfides begin to overgrow a discontinuous aluminum oxide inner scale. At a concentration of 5% chromium the extent of corrosion in 168 h is a factor of 10 greater than for binary alloys. However, in alloys containing 40% chromium, similar chromium additions have no effect on the scale morphology or kinetics. Accordingly, studies are under way to understand the respective mechanisms of alumina and metal sulfide growth on both binary and chromium-containing alloys.

One of the difficulties in comparing the scaling behavior in air with that in H₂S-containing environments has been the inability to obtain identifiable diffraction patterns on the respective scales. Although the scales formed in air are so thin that they are difficult to resolve by conventional X-ray diffraction techniques, the scales formed in our simulated gasifier environment are sufficiently thick that they spall on cooling and therefore can be examined in isolation from the underlying substrate. Nevertheless, such scales, even when retrieved after ≥ 300 -h tests at 800°C, show no discernable Laue spot patterns when examined by X-ray. Because these films are relatively transparent to electrons, they have recently been examined using transmission electron microscopy (TEM),

which has allowed an evaluation of crystallinity, growth epitaxy, and dislocation density. The results to date have indicated that the films are extremely fine-grained, as evidenced by very diffuse scattering patterns. They are, however, crystalline (not amorphous), and the grains are randomly oriented. Energy dispersive X-ray analysis confirmed that films contain principally aluminum with negligible amounts of iron or sulfur. (Oxygen could not be analyzed by the spectrometer used.) Attempts to match diffraction patterns with known aluminum oxide compounds have been hampered by the diffuseness of the patterns, and longer TEM exposure times are now being tried.

An additional approach being used to evaluate processes controlling film growth involves the use of secondary ion mass spectrography (SIMS) coupled with an ^{18}O tracer. Specimens of Fe-28% Al (FA61) and Fe-28% Al-2% Cr (FAS) were oxidized in air for 1 week at 800°C and then were sent to Harwell Laboratory for a similar exposure to air enriched in the stable isotope ^{18}O . After the latter treatment is completed, the specimens will be returned and then examined by SIMS to determine the distribution of ^{16}O and ^{18}O in the resultant oxide films. Examinations will include depth profiling normal to the film growth direction and image analysis using an acute-angle cross section through the film. The objective is to establish whether alumina film growth on iron-aluminum alloys at temperatures lower than 900°C is controlled by anion or cation diffusion and the extent to which molecular diffusion of oxygen may play a role in the mass transfer process.

Following the completion of preoxidation and thermal-cycling tests discussed last period,³ further thermogravimetric studies of Fe_3Al alloys in simulated gasifier environments (H_2S - H_2 - H_2O mixtures) have been temporarily halted in order to modify the gas supply system to incorporate the addition of small amounts of HCl . Although the initial corrosion results for Fe_3Al exposed to an actual gasifier environment showed no effects traceable to the nominal chloride contaminants present in a typical British coal, it is nevertheless important to verify in laboratory tests that the presence of chlorine (specifically, HCl) does not affect the passivity of the oxide film on which sulfidation resistance depends. Furthermore, if chloride-containing reaction products are formed (more likely on cooling at

800°C), they can lead to pitting and general attack as the gasifier is opened to air during downtime periods.⁴ Accordingly, we are adding an additional gas stream with flow controller to feed argon and HCl into our existing gas supply which feeds argon, H₂S, H₂, and H₂O. Gas velocities of the two streams will be controlled to provide HCl concentrations of 500 to 10,000 ppm (by volume) at the specimen. These concentrations are intended to simulate the partial pressures of HCl that are realized in a pressurized gasifier at 40 atm (4 MPa), where HCl concentrations typically range from 50-500 ppm.² Modifications thus far have included several changes in our glass gas supply lines, the replacing of stainless steel bellows with teflon tubes, and the addition of a flow controller that can handle HCl-containing gases.

2.2.2 Investigation of Austenitic Alloys for Advanced Heat Recovery and Hot-Gas Cleanup Systems - R. W. Swindeman, P. J. Maziasz, and E. Bolling

The purpose of this task is to evaluate advanced austenitic alloys for the design, construction, and reliable operation of advanced heat recovery systems and hot-gas cleanup systems. The use of an advanced steam cycle for heat recovery can improve the overall efficiency, thus reducing CO₂ emissions, while the use of a hot-gas particulate cleanup system for pressurized fluidized bed combustors (PBFC) and gasifiers could greatly improve reliability and economics of combined cycle power generation. The material performance requirements vary greatly from one application to the next, but it is clear that a well-developed data base and design methodology would be of considerable benefit in selecting materials of construction. Criteria that go into the materials selection include fabricability, weldability, strength, stability, ductility, corrosion resistance, and cost. A wide variety of alloys designed for specific industrial applications is available for selection and evaluation, but often new alloys must be tailored for advanced systems. Corrosion appears to be the most unpredictable problem because of the ever-changing coal utilization and conversion processes. For this reason strong, ductile, fabricable alloys are being considered for pressure-bearing components, but cladding and coatings of these same materials as tubular products are being examined.

It has been demonstrated that lean stainless steels have outstanding strength and stability for service to 700°C (Ref. 5). Because of the high nickel content required for stability, joining problems were expected. Several filler metals of differing compositions were examined. A high strength 17-14-CuMo stainless steel filler metal was found to be too brittle and a nickel-base filler metal (alloy 82) was found to be too weak.⁵ Promising options were CRE 16-8-2 stainless steel, alloy 556, and alloy 617. In this reporting period, creep rupture testing of specimens welded with CRE 16-8-2 and alloy 556 was extended to times approaching 10,000 h. Most testing was performed on specimens machined from butt welded plates and tubes, and the test sections included base metal, heat-affected zone (HAZ), and filler metal. The plates were in the cold rolled or hot rolled conditions prior to welding, while the tubing was welded in the as-extruded condition and after cold sinking 5, 10, and 12 percent. For comparison purposes, all-weld CRE-16-8-2 data were collected, as well as all alloy 556 weldment data. The results are summarized in Fig. 2.2.2-1 where the log stress to produce rupture has been plotted against the

Fig. 2.2.2-1. Log stress versus Larson-Miller parameter for weldments and weld metal used for joining lean stainless steels.

Larson-Miller parameter (LMP), assuming a parametric constant of 20. Also included in the figure is a line that represents the target strength for the advanced austenitic alloy base metal. Weldments tend to exhibit lower strengths than the target strength at low values of the LMP. This corresponds to low temperatures and short times. At high values of the LMP, the weldment data fall closer to the curve. Weldments produced with the alloy 556 filler metal were significantly stronger than the target strength at high values of the LMP. Most failures occurred in the weld metal.

Often, hot cracks were observed in the base metal HAZ. Usually, these cracks were small, perhaps one or two grain facets, but the potential for cracking in the HAZ of weldments under creep or fatigue conditions was a concern. Since HAZ failures could not be produced in the transverse weldments due to the weakness of the filler metal, the tendency for cracking in longitudinal weldments was examined. Earlier, a longitudinal weldment with CRE 16-8-2 stainless steel filler metal was tested at 650°C. A very high stress, relative to a type 316 stainless steel control specimen, was needed to produce failure. No growth of hot cracks was observed in the HAZ on either side of the weld. A similar longitudinal weldment test was performed at 730°C. The nominal stress was 140 MPa and the specimen failed after 4000 h. Again, failure started with the linking of microcavities in the center of the weld. The crack propagated to the fusion line, at which time the stress on the remaining ligament was estimated to exceed the ultimate strength of the base metal. Plastic instability failure ensued. Post test examination of the HAZ revealed a few hot cracks, but no indication of crack growth. Typical microstructures for the weld metal and HAZ of the base metal are shown in Fig. 2.2.2-2.

2.2.2.1 Identification of Materials for Hot Gas Filter Tubesheets- R. W. Swindeman and E. Bolling

The DOE Morgantown Energy Technology Center (METC) is developing hot gas cleanup techniques for better environmental performance of pressurized fluidized bed combustors (PFBC) and gasifiers.⁶ A barrier filter concept for hot gas filtration of particulate bearing gas has been shown to be feasible in experiments performed at a PFBC facility in Grimethrope, UK, and a larger version is scheduled for construction at a commercial PFBC in Brilliant, Ohio, as part of a collaborative research effort with industry.^{6,7,8}

Y217531

Y217525

Fig. 2.2.2-2. Microstructure in a longitudinally stressed weldment specimen which failed after 4000 h at 730°C and 140 MPa: (a) microcavities in CRE 16-8-2 weld metal region; (b) sound HAZ region.

The system scaleup in terms of capacity and lifetime requires a careful review of the adequacy of the design and materials of construction. The objectives of this work were to evaluate tubesheet designs and materials for the support of ceramic filters, assess alternative designs, collect information on commercial and advanced materials, and recommend a tubesheet material and design methodology for high temperature service.

A two-year program was designed. Early work involved the evaluation of the Grimethrope and alternate tubesheet designs and the collection of data needed for the thermal and elastic analyses of the designs using a simplified thermal cycle.⁹ From the results of this analysis, a reference design was selected for more detailed analysis. Life prediction of the reference design was based on a design-by-analysis approach similar to that developed for high-temperature nuclear components (ASME Code Case N-47). To perform the analysis, it was first necessary to specify analysis and life prediction methods and expand the materials data base to provide input into material constitutive equations and failure criteria. Based on the results of the inelastic analysis, alternative materials and modifications of the design methodology were recommended. The output of the activity was the recommendation of a design methodology, material, and fabrication method.

Under a subcontract to the Oak Ridge National Laboratory (ORNL), Swanson Engineering Associates Corporation (SAEC) examined several concepts for the tubesheet design.^{9,10} From this evaluation, four conceptual designs were identified.⁹ Two designs involved an integral seal and support while two other designs involved a separate seal and support. An evaluation was made of the critical region of each design based on the results of thermal and elastic analyses of behavior during a simplified operational cycle that involved a heating temperature transient from 70 to 1550°F (23 to 843°C) in 12,000 s, a hold period to achieve thermal equilibrium, and a cooling transient.⁹ The critical region (high stress at a high temperature) was generally found to be in the member that joined the hot tubesheet or tubesheet support to the cool vessel. Two designs received special attention - a V-support bellows similar to that incorporated into a gas cleanup vessel at Grimethrope PFBC and the tubesheet-on-ledge design that

was a hot version of a configuration used by Solar Turbines, Inc.⁹ Both configurations produced fairly low stresses at the end of the heating transient. The V-support exhibited the best performance, and is being developed by Westinghouse in some detail. The tubesheet-on-ledge was selected as a promising alternative and was chosen as the reference design for more detailed evaluation. One advantage of the tubesheet-on-ledge design was that no welding would be required. Its simplicity permitted the selection of a high-strength cast material, if needed.

The inelastic analysis and life prediction of the tubesheet-on-ledge design required input from several sources. The inelastic analysis required a load-temperature histogram of the duty cycle, constitutive equations representing the material behavior in a generalized way, and materials data. The life prediction analysis required the output of the stress versus strain computations, the specification of failure criteria, and materials data. The load-temperature-time histogram was obtained from a duty cycle provided by American Electric Power, and was representative of the Tidd plant operation.¹¹ The constitutive equations were based on those developed by Corum, et al.¹² for use with ASME Code Case N-47. These equations were a consistent set of yield, flow, and hardening rules generalized for multiaxial stress states and applicable to arbitrary loading paths. The constitutive equations were embedded in the ANSYS[®] finite element code and have been validated for use at high temperatures for low alloy steels and stainless steels. Not much experience existed with the materials required for service under conditions to be imposed on the tubesheet, and it was beyond the scope of the work to treat this issue in any detail. Much of the materials data was obtained from the alloy vendors. Information required consisted of physical properties (thermal conductivity, specific heat, thermal expansion, density, elastic modulus, and Poisson's ratio) and mechanical properties (yield strength, ultimate strength, and creep behavior). The reference material was selected to be RA333[®]. This alloy was used to construct the tubesheet in the Grimethrope vessel and exhibited a "simple, well-behaved" pattern in regard to the influence of time and temperature on the physical and mechanical properties. It was necessary to expand the data base on RA333 in order to provide all of the information required for analysis. Additional testing

was performed on base metal and weld metal specimens machined from plates of material. Testing included tensile, creep, relaxation, strain- and thermal-cycling. Tensile and creep flow laws were developed and used to produce data in a form required in the structural design specification.¹¹ The ability of the material deformation and hardening models to capture material behavior during thermal transients was examined by comparing the stress response during fully restrained thermal cycling to the response calculated from deformation models. Such a comparison is shown in Fig. 2.2.2-3 for thermal cycling of RA333 between 572°F (300°C) and 1600°F (870°C). The cycle involved a 600-s cooldown, a 300-s hold at the low

ORNL-DWG 91-9633

Fig. 2.2.2-3. Comparison of calculated and experimental thermal cycling data.

temperature, a 900 s heatup, and a 1800 s hold at the high temperature. Deformation was a combination of elastic, plastic, creep, and relaxation, which thoroughly tested the predictive capability of the yield flow and hardening rules. Agreement between the observed and calculated trends were judged to be acceptable. The observed thermal strain was greater than that calculated from the vendor thermal expansion data, but the agreement of the stresses at key points around the hysteresis loop was good. Similar calculations were made to check the ability of ANSYS® to capture the material behavior characteristics, and good agreement was found.¹²

In regard to failure criteria, the rules from ASME Code Case N-47 were examined by Mallett and Fasiczka.⁹ To assure functional integrity, deformation and other limits were specified that covered tensile instability, buckling, gross deformation, fatigue, stress-rupture, creep-fatigue interaction, ductility exhaustion, and non-ductile fracture. Vendor data included stress-rupture and fatigue. Additional data for RA333 were produced for use in evaluating tensile instability, buckling, creep-fatigue, and ductility exhaustion. Notched bars and weldments were tested. Data were only sufficient to show trends, but it was concluded that the creep-fatigue performance was similar to that of alloy 800H, which is included in Code Case N-47. Here, the damage under creep loading, D_c , and fatigue loading, D_f , could be summed independently and added to obtain a total damage fraction D . Failure would occur when D became unity:

$$D = D_c + D_f = 1$$

A few creep-fatigue tests were performed that indicated that failure occurs in RA333 when damage exceeds 1. Moreover, compressive stresses were not nearly as damaging as tensile stresses. A thermal cycle damage calculation was performed for the duty cycle. Damage calculations performed for the actual tubesheet indicated very high creep damage accumulation¹³ and it was decided that RA333 would not be a suitable material.

The possibility was considered that a stronger material would have improved performance under the tubesheet loading conditions. A very wide range of alternate alloys was considered that included stainless steels,

nickel base alloys, cobalt base alloys, and intermetallics. Alloys representative of each class were examined on the basis of the stress versus the Larson-Miller parameter for rupture life, and it was decided that a high yield strength alloy such as an aluminide would be attractive. The data needed to perform the inelastic analyses were lacking. Approximate models for IC221 were developed for plasticity and creep, and calculations were made of the stress versus strain response under the Tidd tubesheet histogram.¹⁴ Results indicated significant potential for the aluminide if it could be produced as a cast plate.

2.2.3 Development of Iron Aluminides - C. G. McKamey, V. K. Sikka, T. Zacharia, S. A. David, and D. J. Alexander

Alloy development of the Fe₃Al-based aluminides during this reporting period has centered on the following tasks: (1) effect of chromium additions on minimizing environmental embrittlement, (2) effect of specimen surface condition on tensile properties, (3) measurement of electrical resistivity, (4) weldability, (5) fabrication, (6) fracture testing of FA-129 alloy, and (7) technology transfer.

2.2.3.1 Effect of Chromium on Minimizing Environmental Embrittlement

The binary Fe-28 at. % Al, with and without 4% Cr, was chosen as the test alloy for studying the role of chromium on minimizing environmental embrittlement. Tensile specimens were punched from the 0.76-mm-thick hot-rolled sheet and prepared using the surface conditions and annealing treatments described in Table 2.2.3-1. As-received (AR) refers to specimens that retain the as-rolled surface oxide; EP refers to specimens whose surfaces were cleaned by first grinding on 320 grit emery paper, followed by electropolishing; and OC refers to the specimens oxidized by heat treating in air. Tensile tests were conducted in air at room temperature using a strain rate of 3.3×10^{-3} /s. For the binary alloy, yield strengths, ultimate tensile strengths, and elongations were relatively insensitive to surface condition within each heat treatment set, indicating no effect of the oxide presence on the tensile properties. The lower yield strengths for specimens heat-treated for 96 h at 500°C are believed to be due to DO₃ ordering. Ductilities for all binary specimens

Table 2.2.3-1. Effect of surface condition and heat treatment on tensile properties of Fe₃Al and Fe₃Al + Cr tested in air at room temperature

Heat treatment (h/°C)	Surface condition at testing ^a	Fe-28Al			Fe-28Al-4Cr		
		Yield (MPa)	Ult. (MPa)	Elong. (%)	Yield (MPa)	Ult. (MPa)	Elong. (%)
1/900+2/700 vac	EP	387	559	4.1	256	364	4.0
	AR	398	587	4.3	199	433	7.8
1/900+96/500 vac	EP	267	515	5.4	192	356	5.8
	AR	277 ^b	551 ^b	5.6 ^b	196	423	7.2
1/850+96/500 air	EP+OC	270	429	3.6	236	483	8.2
	AR	285	466	3.6	248	461	7.0

^aEP - electropolished; AR - as-rolled; OC - oxide coating produced by annealing in air.

^bData from different ingot of same composition.

ranged between 3.6 and 5.6%. Ultimate stress values scaled with the ductility.

Yield strengths of the chromium-containing alloy ranged between 192 and 256 MPa. The lower values compared to the binary are due to a solid-solution softening effect produced by the chromium. Several observations can be made concerning the ductilities of the chromium-containing specimens:

1. The specimens which were electropolished to remove oxide and then annealed in vacuum to minimize oxide reformation (EP) showed elongations comparable to the binary alloy.
2. Leaving the as-rolled oxide coating on the specimens (AR) resulted in an observable increase in ductility for the chromium-containing alloys compared to both the binary and to chromium-containing specimens which had been electropolished.
3. The chromium-containing specimens which were annealed for 1 h at 850°C and 96 h at 500°C in air had comparable ductilities whether they were electropolished (EP+OC) or left with the as-rolled oxide coating.

This suggests that the heat treatment in air produced a thin protective oxide coating on previously electropolished specimens.

4. Also, the ductility values for the chromium-containing specimens annealed in air were comparable to those for the AR specimens, but higher than the ductility of the EP specimens, again suggesting the formation of a protective oxide coating.

The fracture mode is transgranular cleavage in both alloys for all conditions tested. A few specimens showed a mixed failure mode with approximately 5 to 15% intergranular fracture. However, there appeared to be no correlation between the presence of the intergranular failure and the specimen composition, heat treatment, or surface condition.

Our earlier studies had indicated several differences in properties between binary Fe_3Al and the ternary alloy with chromium:

1. Yield strengths were decreased slightly indicating some solid solution softening.
2. The presence of fine wavy slip lines in alloys with chromium as opposed to coarse straight lines in the binary indicated that cross slip from one $\{110\}$ plane to another in the $\{110\}\langle 111 \rangle$ system is easier when chromium is present.
3. The spacing between dislocations in the fourfold superdislocations was increased, indicating a decrease in antiphase boundary (APB) energy.
4. A change in fracture mode was noted with addition of chromium from one of near 100% transgranular cleavage to one of mixed cleavage and intergranular failure, suggesting that chromium enhances cleavage strength and partially suppresses cleavage fracture.

The results of the present study, however, indicate that the beneficial effect of chromium comes from surface-oxide modification, rather than modification of bulk properties. The fact that chromium additions result in improved ductility may indicate a change in oxide chemistry and properties or a change in the kinetics of oxide formation, thereby reducing the water-vapor reaction. Whatever the mechanism, the result is an alloy in which this type of environmental embrittlement is minimized.

2.2.3.2 Effect of Surface Condition on Tensile Properties

The effect of the oxide coating on mechanical properties (its presence or absence, composition, and properties) is one which has not yet been

fully described. In an effort to begin studying this aspect, a series of tensile specimens were prepared with different surface conditions and then tested at room temperature in air. The alloy FAL-VIM 630 (Fe-28Al-5Cr-0.1Zr-0.05B, at. %) produced commercially by Haynes was chosen as the test alloy. The specimens were punched from 0.76-mm-thick sheet which had been stress-relieved for 1 h at 700°C. The surface conditions tested were (1) as-rolled, (2) mechanically ground using 320 grit emery paper, (3) electropolished, (4) chemically etched, and (5) oxidized surface produced by removing as-rolled oxide and then reoxidizing. The as-rolled surface consists of a thick dark-grey oxide produced during the hot-rolling procedure at 30 min/650°. All specimens except those to be tested in the as-rolled condition were mechanically ground using 320 grit emery paper to remove the as-rolled oxide before further surface treatment was performed. All specimens were annealed 1 h at 700°C in vacuum before testing, except the oxidized surface which was annealed at 650°C in air to produce the thin oxide coating. These heat treatments retained the as-rolled microstructure characterized by narrow elongated grains. Table 2.2.3-2 shows that the yield strength was not affected by the surface condition. However, the ductilities averaged about 10% for the as-rolled and mechanically polished conditions, and 15 to 17% for the three conditions that were mechanically and electrolytically polished. This series of tests shows not that the properties are affected by the oxide, but that this alloy suffers from some degree of notch sensitivity. The as-rolled and mechanically polished conditions retained any notches produced in the gage edge during the punching operation, while conditions (3)-(5) were all electropolished before testing which removes or smooths out any notches in the gage edges. To further substantiate this, one specimen which was prepared in the mechanically ground condition was annealed at 650°C to produce a thin oxide on top of the mechanically ground surface; any notches produced along the gage edges during the punching procedure were still there. Its test values were in the same range as those for the as-rolled or mechanically ground conditions. This result is opposite to the result of the chromium studies described above which showed less ductility with electropolished surfaces, suggesting that other factors are involved such as microstructure and composition. Determining the effects of surface oxide will require further tests.

Table 2.2.3-2. Effect of surface conditions on room-temperature tensile properties of Fe₃Al^a

Elongation		0.2% Yield	Ultimate
Surface condition	(MPa)	(MPa)	(%)
As-rolled oxide	564.7	851.5	11.4
Mechanically polish (ME), 320 grit	603.3	870.1	9.8
Electropolish (EP), ME+EP	583.3	975.0	15.3
Chemical etch (CE), ME+EP+CE	583.3	1036.3	16.9
Oxidized surface (OX), ME+EP+OX, (3) 30 min/650°C	601.9	1048.0	17.1
ME+OX (no EP)	565.4	794.3	8.6 ^b

^aAlloy FAL-VIM 630 (Fe-28Al-5Cr-0.1Zr-0.05B, at. %). Specimens were heat treated 1 h/700°C in vacuum, unless otherwise noted. Test conducted in air using a strain rate of 3.3×10^{-3} /s.

^bOnly one test performed.

2.2.3.3 Measurement of Electrical Resistivity

Literature values for physical property measurements on iron-aluminide alloys are very sparse. With time and available equipment permitting, we have begun to measure some properties. The electrical resistivity as a function of temperature to 1000°C in air was measured for FAS (Fe-28Al-2Cr-0.05B, at. %) and FA-133L (Fe-28Al-5Cr-0.5Nb-0.5Mo-0.1Zr-0.2B). Although no metallography has been performed to determine grain size, the specimens were heat-treated to produce complete recrystallization (1 h/750°C + 1 h/950°C). Figure 2.2.3-1 shows that the resistivities for both alloys are high (160 to 200 $\mu\Omega$ -cm) compared to steels (<120 $\mu\Omega$ -cm) and do not vary significantly with temperature. These results suggest their use for electrical and/or magnetic applications.

Fig. 2.2.3-1. Electrical resistivity versus temperature for alloys FAS (Fe-18Al-2Cr-0.05B, at. %) and FA-133L (Fe-28Al-5Cr-0.5Nb-0.5Mo-0.1Zr-0.2B).

2.2.3.4 Weldability

Welding is a major area of concern for realizing the potential benefits of the unique properties of iron aluminides. The welding processes used must be capable of producing high quality weldments under field and shop conditions which are free of defects, have good mechanical properties in comparison to the base metal, and be compatible with the unique properties of the base metal. Initial work on the weldability of iron aluminides has identified some inherent problems associated with these alloys. These include a propensity for hot cracking, a propensity for cold cracking, and a possible degradation of the mechanical properties of the weldment in comparison to the base metal.

Preliminary results indicate that alloy FA-129 (Fe_3Al) modified with Cr, Nb, and C appears to have better welding characteristics than any of the other alloys studied so far. Welds with minimum hot cracking were produced in this particular alloy. However, the studies have also shown that iron aluminides are very sensitive to minor changes in composition of the base metal. As described in the previous report, this was evident from the test results obtained for FA-129 (heat 13837). In this heat, the inadvertent addition of 300 ppm boron instead of carbon caused the material to crack severely during welding.

In addition, the iron-aluminide alloy has shown some tendency for cold cracking. Cold-cracking sensitivity in welds is primarily related to the dissolved hydrogen in the weldment. Typically, hydrogen is carried to the arc atmosphere by the shielding gas, flux, or surface contamination. This hydrogen is converted to the atomic or ionized state and readily dissolves in the weld metal. Several factors, including the amount of dissolved hydrogen, the thermal stresses generated and the ductility and strength of the material, influence the sensitivity to cold cracking.

Recently, the weldability of two heats of FA-129 (Heat 13878 and Haynes experimental alloy) was investigated. These heats have the same nominal composition as the experimental heat FA-129B studied earlier. The material was vacuum induction melted and obtained in thin sheet form (nominally 0.76 mm). As a preliminary screening test for the weldability of the material, autogenous gas-tungsten arc (GTA) and electron beam (EB)

melt runs were made at welding speeds ranging from 12.7 to 101.6 cm/min. Visual inspection of the welds showed no observable cracks in any of the welds at a magnification of 10× under light microscopy.

Following the screening tests, SigmaJig tests were conducted to evaluate the weldability of these heats. The results showed a threshold cracking stress of 82.7 MPa for heat 13878 and 103.4 MPa for the Haynes alloy. These values are considerably lower than the threshold stress of 172.4 MPa obtained for the experimental heat FA-129B studied earlier.

In addition, the weldability of three experimental heats of Fe₃Al alloys with good creep strength (FA-123, -130, and -133) was also evaluated. All of these alloys cracked severely during preliminary screening tests with no applied stress. Consequently, SigmaJig tests were not performed.

Recently, there has been some reports of successful welding of nickel aluminides using alternating current (ac) welding processes. Consequently, autogenous melt runs were made on several heats of iron aluminides using the ac welding process. The results of the study showed negligible influence on the weldability of the material. If anything, it seems to increase the cracking tendency of FA-129. However, it must be noted that the cleaning action of the alternating current produced somewhat cleaner-looking welds.

Following these studies, the weldability of 6.35-mm-thick (0.25-in.) FA-129 (Heat 13989) plate material was investigated. Initially, autogenous GTA and EB melt runs were made at two different welding speeds. Delayed (after 24 h) cold cracking (Fig. 2.2.3-2) was observed in the GTA welds. Optical metallography revealed these cracks to be a mixed cleavage type (both intergranular and transgranular) in nature.

Additional welds were made on the 6.35-mm-thick material using FA-129 filler metal in a groove that had a 90° included angle and a 1.6-mm (1/16-in.) root opening. The welds were made using ac with argon shielding and backing gas. The welds looked very clean and did not show any cracks immediately following welding. However, delayed cold cracks (Fig. 2.2.3-3) were observed in the weld metal extending to the heat-affected zone (HAZ) and the base metal of the specimen. Figure 2.2.3-4 shows scanning electronmicroscopy photomicrographs of a typical cracked surface of the weldment indicating cleavage fracture.

Y217284

Fig. 2.2.3-2. Optical micrograph showing delayed cold cracking (after 24 h) in GTA weld of Fa-129 (Heat 13989).

Y217467

Fig. 2.2.3-3. Optical micrograph showing delayed cold cracking in weld of FA- made using FA-129.

Fig. 2.2.3-4. Fractograph of a typical cold-cracked surface indicating cleavage fracture.

2.2.3.5 Fabrication

Melting and fabrication of FA-129 alloy continued. A total of six heats were prepared at ORNL by the VIM process. Each heat weighed 7.5 kg (15 lb) and was cast into a 7.6-cm-diam (3-in.) graphite mold. Three ingots are shown in Fig. 2.2.3-5 to demonstrate the excellent surface quality observed for these ingots. None of the ingots showed any visual signs of porosity or cracks. Detailed metallography of these ingots is currently in progress. All of the ingots were extruded at 900°C to a 18-mm-thick rectangular bar. Photomicrographs of the extruded bar are shown in Fig. 2.2.3-6. The bar was subsequently rolled at 800°C to a thickness of 2.5 mm.

YP11197

Fig. 2.2.3-5. Photograph showing the surface quality of vacuum-introduction, melted ingots of FA-129.

Fig. 2.2.3-6. Optical microstructure of as-extruded sheet bar of the alloy FA-129 (Heat 14064) prepared by VIM. The extrusion was at a temperature of 900°C and area reduction ratio was 6:1 (a) bar edge, (b) half-way to the bar center, and (c) bar center.

Generally, three rolling passes of 15% reduction each were possible prior to reheating. The 2.5-mm-thick sheet was further rolled at 650°C to 0.76-mm-thick sheet. Both the sheet and plate were supplied for welding and toughness tests at ORNL, and toughness and crack-growth tests at Rensselaer Polytechnic Institute. The 0.76-mm-thick sheet was also used at ORNL for mechanical properties tests. The creep testing of FA-129 and other alloys have continued. Several tests have reached test times exceeding 5000 h. Data from these tests are shown as a Larson-Miller plot in Fig. 2.2.3-7. Creep data for type 304 stainless steel, type 403

Fig. 2.2.3-7. The comparison of creep rupture properties of Fe₃Al-based alloys with Thermenol, type 403 stainless steel, and type 304 stainless steel. Tests were conducted in air in the temperature arrange of 450 to 700°C.

stainless steel, and an old iron-aluminide alloy known as Thermenol are also included for comparison. Note that the creep-rupture strengths of the ORNL-developed ductile iron aluminides generally matches that of type 403 stainless steel. One of the iron aluminides shows strength close to type 304 stainless steel. Current effort is devoted to optimizing a composition that will match the creep strength of type 304 stainless steel and still show adequate ductility at room temperature, toughness at a low temperature, and acceptable weldability.

2.2.3.6 Fracture Testing of FA-129 Alloy

Preliminary fracture testing of alloy FA-129 has been conducted to determine baseline fracture properties in conjunction with a series of planned tests on the effect of environment on the fracture properties of these alloys. Initial testing included half-size Charpy impact tests to determine the ductile-to-brittle transition temperature (DBTT).

The material tested was fabricated at ORNL by the Metalworking Theory and Practice Group. A 72-mm-diam ingot (Heat 13989) was vacuum induction melted and extruded at 900°C into a bar approximately 19-mm-thick by 60 mm wide. A portion of this bar was hot-rolled at 700°C to approximately 13-mm-thickness. Half-sized Charpy impact specimens 5 × 5 × 25.4-mm-long were machined from this bar using oil coolant during all machining operations. The specimens were then heat treated in air for 1 h at 700°C and oil quenched. Specimens were oriented parallel to the extrusion direction, and notched so that crack growth was either across the bar or through the bar thickness (LT and LS orientation, respectively), or perpendicular to the extrusion direction, and notched so that crack growth occurred either along the length of the bar or through the bar thickness (TL and TS orientation, respectively). Testing was carried out on an impact tester adapted for subsize specimen testing. The specimens were heated with a hot air gun for temperatures up to 300°C. Higher temperatures were attained by soaking the specimens in a small box furnace. When the desired temperatures were reached, the specimens were transferred with tongs to the test machine anvils as quickly as possible (about 4 s) and then broken.

The results of the impact testing are shown in Fig. 2.2.3-8. The first batch of specimens were notched in the LS and TS orientations [Fig. 2.2.3-8 (a)].

Fig. 2.2.3-8. Absorbed energy versus temperature for half-size Charpy impact specimens of FA-129: (a) LS and TS specimens and (b) LT and TL specimens.

These specimens were machined into bars, heat-treated, and then notched. The values of absorbed energy are quite low, and begin to rise at about 450°C. Part of the reason for the low energy levels is the small specimen size. Full-size specimens would be expected to absorb about seven times as much energy. The very high temperatures necessary to see an increase in the energy absorption are of concern. An interesting feature is the apparent peak in energy at 600°C.

The TL and LT specimen results are shown in Fig. 2.2.3-8 (b). Four sets of data are presented. Some specimens were tested without having been given the final heat treatment. The remainder were machined, notched, and then heat-treated. Heat treatment after notching resulted in an increase in the energy absorbed. However, these specimens absorbed somewhat less energy than the LS and TS specimens.

The low values of absorbed energy and the very high temperatures required before the energy levels begin to increase indicate that this alloy suffers from low toughness. Preliminary examination of the fracture surfaces revealed that the low-temperature fracture mode was transgranular cleavage, with ductile fracture occurring at higher temperatures. Deep splits apparently along grain boundaries were observed parallel to the rolling direction.

The LS and TS specimens showed higher energy levels than the LT and TL specimens, at high temperatures. This difference is due to the anisotropy in the material. Metallographic examination revealed that the microstructure consisted of very large pancake grains elongated in the direction of extrusion and rolling. The deformation during extrusion is insufficient to prompt dynamic recrystallization, and so the large grains remain. This anisotropy and the weak grain boundaries account for the difference observed between the LS and TS results and the LT and TL data. The LS and TS specimens are oriented so that a crack grows down through the layers of pancake grains. The weak grain boundaries will tend to deflect and arrest the crack, resulting in higher energy levels for these orientations as compared to the TL and LT orientations when ductile fracture modes dominate at higher temperatures. At lower temperatures where a cleavage mode of fracture dominates, the difference between the orientations is minor.

The metallographic examination also revealed the presence of a second phase. Energy dispersive X-ray analysis indicated that the particles were rich in iron and niobium. These particles were either grouped in clusters of small round particles or were present as long isolated bars or plates. In both cases, the particles were strung out in the rolling direction. Many of the small round particles were broken in two, whereas the long rods were cracked in numerous locations. Apparently these particles were broken during the hot rolling at 700°C. At this temperature the matrix is ductile, so the cracks were arrested. However, on subsequent testing at lower temperatures, these brittle particles will readily generate cracks which will propagate into the now brittle matrix. These particles are believed to be partially responsible for the low energy levels, along with the large grain size.

The presence of these niobium-rich particles indicates that there is excess niobium present in this alloy. This may be due to incomplete homogenization, which has not allowed sufficient time at temperature for the niobium to diffuse throughout the matrix. The limited amount of deformation possible in extrusion from the 72-mm-diam ingot to the 19-mm-thick bar will not adequately break down the as-cast structure, and diffusion distances will remain large. This will necessitate longer soaking times and/or higher temperatures to permit the niobium to become homogeneously distributed.

Another possibility is that there is excess niobium in the alloy. The niobium content is intended to be similar to the carbon content to allow niobium carbides to be produced. However, there is much more niobium (0.5 at. %) than carbon (0.2 at. %) in this alloy composition. It may be possible to reduce the niobium content significantly, and thus prevent the occurrence of the brittle second phase without decreasing the number of beneficial chromium carbides in the matrix.

Further testing of the present alloy FA-129 material has been terminated due to the presence of the second phase particles. Additional testing to determine the fracture toughness of this alloy and the effects of environment on the fracture is planned if suitable material can be provided.

2.2.3.7 Technology Transfer Activities

A strong effort continued in working with industry towards developing applications and the sources of producing and fabricating Fe_3Al -based iron aluminides. A technology transfer meeting on iron aluminides was held in Oak Ridge, Tennessee, on August 14-15, 1990. Approximately 33 attendees from diversified interests were present. In addition to this meeting, the following specific activities continued with individual companies.

2.2.3.7.1 Ford Motor Company

The evaluation of Fe_3Al alloys containing molybdenum for exhaust system applications continued. Compared to molybdenum-free compositions, no pitting was observed. Tests completed thus far simulate 4-year life and are continuing to simulate 10-year life. The results are provided to ORNL on a periodic basis.

2.2.3.7.2 Dresser-Rand Corporation

Dresser-Rand is interested in evaluating the iron aluminides for steam-turbine application. They would like to take advantage of the lower density of iron aluminide compared to the 12% Cr steel currently used. However, prior to their final decision, Dresser-Rand wanted to conduct stress corrosion cracking tests in steam and steam with impurities such as NaOH. Such testing has been completed by Dresser-Rand on ORNL-supplied iron aluminide. A recent report of results from Dresser-Rand indicated that the iron aluminide passed stress corrosion cracking tests in both environments. Dresser-Rand would now like to fabricate a prototype steam turbine rotor. The fabrication of such a rotor will provide Dresser-Rand with the first-hand experience in machining iron aluminide and its assembly into complex parts.

2.2.3.7.3 PALL-Trinity

PALL-Trinity has been working with iron-aluminide powders to fabricate porous metal filters for hot-gas cleanup. As powder production goes into effect, PALL will fabricate large filters for actual testing.

2.2.3.7.4 Ametek Special Products Division

A commercial source for powder of iron aluminide is needed for the fabrication of porous filters and for spray-coating applications. Ametek already has experience with the powder production of a 1100-kg (500-lb) heat of iron aluminide. This powder has been supplied to various potential users. Ametek is currently negotiating a license with ORNL for the production of iron-aluminide powder. Ametek is currently working with coating companies to develop procedures for coatings of iron aluminides on various base materials.

2.2.3.7.5 Wisconsin Centrifugal

A fabricator of centrifugal-cast tubing and piping, Wisconsin Centrifugal has taken a very strong interest in the melting and casting of iron aluminides. Wisconsin Centrifugal has been given the technical data and guidance for potential applications. Internally, they have made a commitment to melting and casting, using their own funds. ORNL will help them with compositions to be melted, the recovery of various elements, mechanical properties, and microstructural characterization. Wisconsin Centrifugal is also currently estimating the cost per pound for the Fe₃Al-based iron aluminide.

2.2.3.7.6 Kiln Applications

After mining, ores are often dried. The drying operation is carried out in kilns at 500 to 700°C. The drying operation releases sulfur containing gases, which are highly corrosive to currently used kiln materials. The superior sulfidation resistance of iron aluminides offers an excellent choice for this application. This application is being pursued through the help of Michigan Tech.

2.2.3.7.7 Air Products and Chemicals

Air Products has a process for making oxygen based on a reversible reaction of oxidation and deoxidation of molten sodium nitrite salt. In this process, when air is passed through sodium nitrite at 482°C, oxygen is preferentially absorbed to form sodium nitrate. When the nitrate salt is

heated to 650°C, the salt turns back to nitrite and high-purity oxygen is released. One major deterrent towards commercialization of this process is the highly corrosive nature of sodium nitrite/nitrate salt. Iron aluminide based on Fe_3Al and FeAl have been found to offer the most corrosion resistance in this salt at potentially the lowest possible price. However, to build the first plant for oxygen production, iron aluminides need to be commercialized with inclusions in the proper ASTM specifications, ASME codes, and AWS specifications. A plan to commercialize the Fe_3Al alloys is being jointly prepared by Air Products and ORNL.

2.2.3.7.8 The Timken Company

Timken is a producer of seamless tubes by the hot-piercing process. Timken is interested in being a source for seamless tubes of iron aluminide. They have committed their funds to melt, process, and test the ORNL-developed composition. Timken's initial experience with ORNL-supplied material was excellent. However, when melted in their laboratory, Timken experienced some problems with casting porosity and cutting cracks. ORNL is currently working closely with Timken to determine the cause of their observations.

2.2.3.7.9 Harrison Alloys

Iron aluminides have very high electrical resistivity, which is independent of test temperatures up to 1000°C. This behavior makes iron aluminides potentially suitable for heating elements. Harrison Alloys is a company that makes heating elements. ORNL has supplied the rod of Fe_3Al alloy to them for their evaluation of its processing and performance as heating elements. If Harrison Alloys is satisfied with the heating-element performance, they would like to receive a license from ORNL.

2.2.3.7.10 Precision Rolled Products

This company deals with vacuum-induction melting (VIM), electroslag remelting (ESR), and rolling the ingots to bars of various shapes. The VIM furnace has a capacity of 13,200 kg (6000 lb), and 40-cm-diam (16-in.) ESR ingots are possible from a heat of this size. This company has shown very

strong interest in melting 13,200-kg heats of iron aluminide. In fact, they have quoted ORNL a price at which they can make the alloy. ORNL intends to consider Precision Rolled Products as one of the suppliers during the scaleup of iron aluminides.

2.2.3.7.11 Others

Many other potential users, producers, and fabricators of iron aluminides are currently being contacted. These include: Metallamics, Inc., Aerospace Corporation, AKZO, International Paper, Union Carbide, EPRI, Hoskins Manufacturing, and Special Metals.

2.3 CORROSION AND EROSION RESEARCH

2.3.1 Responses of Metallic and Oxide Surfaces to Deformation - Mukund Rao, J. R. Keiser, and P. F. Tortorelli

This project has been divided into two tasks, both of which involve the deformation of surfaces. The first task (Erosion Studies) addresses the deformation of metals and alloys during erosion and erosion-corrosion. The second task consists of a study of the mechanical properties of oxide scales formed on the surface of selected metals and alloys.

2.3.1.1 Erosion Studies

The near-surface deformation behavior in metals and alloys during erosion was studied using a multi-pronged approach. The issues addressed can be divided into three major categories: multiple-particle erosion of metals and alloys, single-particle impacts on metallic surfaces, and single-particle impacts on scales formed on eroded-corroded surfaces.

2.3.1.2 Erosion Behavior of 1100 Al and Fe₃Al Alloys

Samples of annealed 1100 Al and heat-treated Fe₃Al were eroded in a rotating-arm apparatus at the University of Notre Dame using spherical steel shot 297-420 μm in diameter. Particles were accelerated to a velocity of 45 m/s and impinged on the sample at angles of 30°, 60° or 90°. To examine the progress of erosion, tests were interrupted and samples removed after various levels of erodent dosage between 10 and 480 g. Mass loss measurements were made to an accuracy of 0.01 mg. Figure 2.3.1-1 shows the results of the erosion tests; negative numbers signify a mass gain in the sample. At 30° incidence, both materials achieved steady-state, erosion rates with the Fe₃Al eroding about 2.5 times slower than the 1100 Al. At 60° and 90° incidence, only the Fe₃Al samples showed mass loss. The 1100 Al samples experienced a steadily increasing mass gain, which was found to be due to severe embedment of fragments of erodent particles.

The surfaces of the eroded specimens were examined in a scanning electron microscope (SEM) equipped with an energy dispersive X-ray analysis (EDXA) system. Longitudinal sections of each sample were then mounted metallographically in 3:1 taper sections. A mechanical properties micro-

Fig. 2.3.1-1. Erosion test results for 1100 Al and Fe₃Al eroded with 297 to 420- μ m-steel shot at 45 m/s.

probe (MPM) was used to measure the hardness below the eroded surfaces on polished and lightly etched taper sections.

Figure 2.3.1-2 shows micrographs of surfaces of the two materials after erosion at 30° and 90°. The highest dose for each test condition is shown. At 30° incidence, the 1100 Al develops a characteristic rippled surface topography which has been examined in detail in a previous study.^{15,16} At 90°, a hill and valley topography is seen in 1100 Al. In contrast, the surfaces of Fe₃Al eroded at 30° and 90° appear relatively featureless, and it is more difficult to pick out individual impact sites on the surfaces. Material movement and surface damage are much less than for 1100 Al.

Figure 2.3.1-3 shows taper sections of 1100 Al and Fe₃Al eroded at 30° incidence. Wave crests and valleys are clearly seen in the 1100 Al, but the surface of the Fe₃Al alloy appears very flat. Breaking wave crests in the direction of particle impingement cause material loss in the softer aluminum alloy. As was shown in the previous study,^{15,16} material is apparently pushed up from the wave valleys into the wave crests, extruded out in the form of lips on the crest and finally fractured. Such a mechanism cannot be identified for the Fe₃Al alloy.

At 90° incidence, the Fe₃Al alloy showed a slightly rougher surface in the taper sections than for 30° incidence, but relatively smooth compared to eroded 1100 Al surfaces. At this angle of impingement, the 1100 Al was embedded with fragments of the erodent particles, as seen in the cross section shown in Fig. 2.3.1-4. The embedded regions were determined by EDXA to contain erodent particle material. These fragments were much smaller than the erodent particles and were probably pieces of oxide scale removed from the particle surfaces as well as broken pieces of particles contained in the original mixture. In addition, the embedment was concentrated in the valley regions of the hill and valley topography, as seen in Fig. 2.3.1-4. The swirling pattern of the embedded fragments indicated that material was being pushed down into the valleys and back-extruding into the hills.

Figure 2.3.1-5 shows the results of MPM measurements on taper sections of Fe₃Al and 1100 Al. The data for 1100 Al is from a valley region formed at 90° incidence and shows that hardness increases continuously to a maximum

M31228

1100 Al

200 μm

M31222

M30986

Fe_3Al 100 μm

M30988

Fig. 2.3.1-2. (a) 1100 Al has a rippled surface after erosion at 30° and (b) a hill and valley topography after erosion at 90°. Fe_3Al surfaces show less damage at both angles: (c) 30° and (d) 90°.

M31219

M31221

Fig. 2.3.1-3. Micrographs of taper sections 1100 Al (a) and Fe₃Al (b) eroded at 30° incidence. Erosion direction is from the upper left and erodent dose is 300 g.

Fig. 2.3.1-4. Cross section of 1100 Al sample eroded with 480 g of steel shot showing erodent material embedment in valleys.

Fig. 2.3.1-5. Results of MPM measurements on taper sections of eroded 1100 Al and Fe₃Al. The distances have been corrected for the taper.

at the surface. Considerable scatter in the data is due to the presence of embedded fragments as well as due to interference from neighboring hills and valleys. A hardness profile under a hill showed a similar trend, except that the depth of hardening was greater. In other words, a greater volume of hardened material existed under a hill than under a valley, supporting the idea that material was back-extruded into the hills. Results from 30° incidence are not shown here as they have been discussed in detail in previous publications.^{15,16}

The MPM data from the Fe₃Al alloy shows markedly different behavior. As in 1100 Al, hardness increases towards a maximum on approaching the eroded surface from the bulk. However, the maximum hardness is reached at some distance below the surface, and then falls off as the surface is approached. Similar trends are seen for both 30° and 90° incidence. The lack of a rippled or hill and valley topography implies that this behavior is not restricted to some localized areas on the surfaces. These results indicate that thermal recovery mechanisms may play an important role in the deformation and erosion of this material. The reason that similar behavior is not seen in the 1100 Al alloy may be related to fundamental issues such as ductility, hardness and thermal properties.

The analysis of the data is near completion and the results will be reported in detail in upcoming publications.

2.3.1.3 Single-Particle Impact Studies to Determine Effect of Energy Input on Erosion of 1100 Al and Fe₃Al Alloys

A single-particle gas gun was designed and built for erosion studies by ORNL's Fusion Energy Division. The gun incorporates technology used to fire pellets into the plasma in fusion reactors. A fast-acting solenoid valve creates a short pulse of high-pressure gas which is used to propel a plastic sabot at velocities up to 2000 m/s. The sabot carries particles up to 1 mm in diameter with no constraint on particle geometry. These sizes are smaller than most previous single-impact studies and more representative of sizes encountered in fossil energy systems. A scraper near the end of the barrel separates the particle from the sabot, so that the particle continues its trajectory and strikes the sample at a preset angle. The velocity of the ball is determined from the time delay between signals from

shock transducers triggered by impacts on the sabot scraper and the target sample.

The gun was used to shoot single 343- μm -diam WC balls on targets of annealed 1100 Al and Fe_3Al . Impacts were made at 30° and 90° angles. The highest velocity utilized was 894 m/s. Craters were examined optically and in the SEM. For 90° impact craters, the samples were mounted metallographically and sectioned so as to expose the craters in cross section. The extent of hardening beneath the craters was measured using a MPM.

Figure 2.3.1-6 shows the results of a 90° impact on 1100 Al at 894 m/s. At this high velocity, the ball penetrated about 1 mm and remained embedded in the sample. Also shown in the figure is the hardness profile beneath the crater, drawn on the same scale as the micrograph. Similar results for a 794 m/s impact are shown in Fig. 2.3.1-7 for the Fe_3Al alloy. In the case of 1100 Al, the maximum hardness seen in the subsurface regions is less than two times the bulk hardness. This is less than the peak hardness measured in specimens undergoing multiple-particle erosion at substantially lower velocities (see Fig. 2.3.1-4). In contrast, the peak hardness measured for the Fe_3Al is similar to the multiple-particle results in Fig. 2.3.1-4. In both materials, the distance over which hardening occurs is significantly greater than that seen in lower velocity multiple-particle impact studies. Both materials show softening in a region within approximately 200 μm of the surface, but the evidence is much more conclusive for Fe_3Al . The aluminum alloy seems to show some additional hardening at greater depths, but this result is believed to be an artifact since data at these depths were obtained from single measurements while results shown for shallower depths are averages over several indentions. The Fe_3Al hardness profile is closer to profiles measured in multiple-particle erosion tests at lower velocities. The higher hardness and lower thermal conductivity of Fe_3Al restricts deformation and associated heat to smaller volumes than in 1100 Al. As a result, thermal effects in aluminum are felt only at higher velocities and tend to be spread out over a larger volume. In contrast, since these effects are seen over smaller volumes for Fe_3Al , they occur at both low and high velocities.

YP11357

Fig. 2.3.1-6. Cross section of a 1100 Al sample impacted by a single 343-μm WC ball at 894 m/s along with an MPN hardness profile beneath the crater and embedded ball. The distance scale on the hardness profile is the same as on the micrograph.

YP11356

Fig. 2.3.1-7. Cross section of a Fe₃Al sample impacted by a single 343-μm ball at 794 m/s along with an MPM hardness profile beneath the crater. The distance scale on the hardness profile is the same as on the micrograph.

Figures 2.3.1-8 and 2.3.1-9 show craters formed at various velocities at 30° incidence in 1100 Al and Fe₃Al, respectively. Much larger amounts of deformation are seen in the softer aluminum. In addition, the high ductility of the material causes large lips to be formed and material removal does not always occur. No evidence of melting is seen, as has been reported in the literature for impacts from larger particles.¹⁷ An energy balance shows that the 343- μ m balls used in the present study have less than 0.5% of the energy of 5-mm balls typically used in studies reporting melting. In the case of Fe₃Al, impacts are much smaller and also show less damage. The lips of material extruded out in front of the crater are smaller and often fracture due to the limited ductility of this alloy. Thus, although material removal mechanisms are similar in both cases, the higher ductility of 1100 Al helps to delay material removal by impacts from spherical particles.

These results are preliminary and studies are continuing in order to more closely identify velocity and material property effects on the impact response of materials.

2.3.1.4 Single-Particle Impact Characterization of Erosion-Corrosion Scales on Steels

Levy and coworkers at Lawrence Berkeley Laboratory¹⁸⁻²⁰ have found that small additions of silicon to various steels significantly increased their erosion-corrosion resistance. The reason for this beneficial effect is unknown at the present time. This study was undertaken to determine if silicon additions to steels modified the impact response of erosion-corrosion scales.

Samples of 2.25Cr-1Mo(<0.5Si) and 2.5Cr-0.55Mo-1.4Si steels were eroded-corroded at Lawrence Berkeley Laboratory at 450 and 650°C using fluidized-bed combustor bed particles at velocities of 10 and 20 m/s. The steel with higher silicon showed significantly lower metal loss rates under all conditions.

The samples were subsequently subjected to single-particle impacts using spherical WC particles at velocities around 50 m/s. Crater volumes were computed from profilometer traces across the impact craters. As determined by SEM/EDXA, all scales were composed of oxidation product and

M31237

M31236

200 μm

M31238

Fig. 2.3.1-8.
1100 Al samples im-
pacted by single 343- μm
WC spheres at 30° inci-
dence and velocities of
340 m/s (a) and 625 m/s
(b) and (c).

M31241

M31242

Fig. 2.3.1-9. Craters formed on Fe_3Al samples by single $343\text{-}\mu\text{m}$ WC spheres impacted at 30° incidence and velocities of (a) 280 and 340 m/s and (b) 450 m/s.

deposited bed material erodent. Crater volumes were normalized with respect to the square of their respective velocities to correct for velocity variation effects. Figure 2.3.1-10 shows the normalized volume comparison between the two steels and there is no apparent consistent

ORNL-DWG 90-17100

Fig. 2.3.1-10. Single-particle impact crater volumes corrected for velocity variations compared between 2.25Cr-1Mo and 2.5Cr-0.55Mo-1.4Si steels.

effect of silicon content. At 450°C, the high silicon steel appears to be more impact resistant. However, in about half the cases at 650°C, the same steel showed larger craters. What is more evident is that, for both steels, the smallest craters were made on scales formed at the lower test temperature (450°C).

Figure 2.3.1-11 shows low-magnification micrographs of single-impact craters on the scales. Sample designations are as in Fig. 2.3.1-10. The scales around the craters are typically continuous in appearance except for sample A-1, which is clearly segmented (sections of the scale are clearly delineated from each other by a network of thin cracks/grain boundary-like features; such scales have been experimentally associated with low erosion-corrosion rates¹⁸⁻²⁰). Sample A-4 was also segmented, but to a lesser extent. Sample A-9 has no scale, it apparently having spalled during the erosion corrosion test itself. Samples A-12 and A-1 exhibit widespread spalling around the single-impact craters and the spalled area is generally more irregular for A-1, the sample with a segmented scale. No material appears to be lost from within the craters. The other samples show no damage to the scales, both within and around the impact craters. Within the craters, scales are significantly compacted and smoothed by the impacts.

High-magnification micrographs from inside the craters showed many cracks in samples A-4 and A-1, which were the samples with the most segmented scales. Only occasional cracks were seen in the other samples. In addition, scales formed at the lower test temperature (450°C), samples A-16 and A-13, appeared to have undergone the least amount of scale compaction/smoothing within the single impact craters.

MPM measurements on cross-sectioned craters showed that there was no difference between the steels or test conditions in terms of the hardening response to single impacts. The sections also showed significantly thicker scales on samples A-12 and A-1, which were the samples which spalled under single impacts.

The appearance and thickness of the scales could be related to the single-impact response of the steels. Samples eroded-corroded at 450°C had denser, more mechanically stable scales which could be associated with the lower erosion-corrosion rates at this temperature. At 650°C, the scales were less dense, which resulted in apparent ductility by permitting them to densify under impact. Thick continuous scales maintained their integrity under the lower velocity conditions of the erosion-corrosion tests, thus leading to low metal losses, but spalled catastrophically under the single impacts. Segmented scales spalled in smaller pieces under single impacts,

Fig. 2.3.1-11. Micrographs showing appearance of single-particle impact craters on the various samples (refer to Fig. 2.3.1-1 for sample designations).

and it is proposed that they would exhibit significant failure under low velocity multiple-particle conditions, thus providing less protection to the steels than continuous scales under similar conditions. The reverse would be true at higher velocities. This situation is depicted in Fig. 2.3.1-12. The superior erosion-corrosion resistance of silicon-containing steels could not be related to the impact behavior of their scales.

ORNL-DWG 90-17101

SEGMENTED SCALE (LOW AND HIGH VELOCITIES)

**CONTINUOUS SCALE
(LOW VELOCITY)**

**CONTINUOUS SCALE
(HIGH VELOCITY)**

Fig. 2.3.1-12. Sketch showing how segmented scales may not always be more protective than continuous scales.

These results have been documented in a paper entitled "*Mechanical Behavior of Erosion-Corrosion Scales on Steels as Characterized by Single Particle Impacts*," by Mukund Rao, James Keiser, Alan Levy, and BuQian Wang and was submitted for publication to *Wear*.

2.3.2 Mechanical Properties Of Oxide Scales

The high-temperature corrosion resistance of metals and alloys is directly related to the presence of a protective surface oxide scale that is either inert to, or slowly reactive with, the environment. Accordingly, the mechanical integrity and properties of the oxide are of considerable importance in understanding and controlling oxidation, scale spallation, and the interaction between chemical and deformation effects. To this end, measurements of certain mechanical properties of oxide scales by a submicron indentation technique are being undertaken. Such results can be used in calculations of fracture energies and toughness of oxide scales and in the determination of the limits to scale adherence.²¹⁻²⁶ This information can ultimately aid in the design of high-temperature, corrosion-resistant materials using both the chemical and mechanical properties of the scale as a basis for compositional and other modifications to a particular alloy system. Furthermore, the results can also influence alloy development as a result of forming scales that protect the bulk metallic material from environmental degradation by blocking the uptake of deleterious species (for example, hydrogen).

The elastic and plastic properties of chromia-rich and alumina scales are measured with a mechanical properties microprobe (MPM), which utilizes a depth-sensing submicron indentation technique that has recently been successfully applied to mechanical characterization of thin films²⁷ and oxide scales.^{28,29} The MPM is a modified version of a commercial instrument known as a Nanoindenter and its present use has been described elsewhere.²⁹ Results for chromia-rich scales on stainless steels have been reported previously,^{28,29} as have some initial data for scales formed on Fe-36 at. % Al (FeAl). More recently, work has focused on Fe₃Al and the first mechanical properties data for scales grown on Fe-28 at. % Al have now been obtained. The Fe₃Al specimens were oxidized for greater than 200 h in dry air at 900°C in a microbalance system. In this way, weight gain was

continuously monitored. Thin (approximately $1.5\text{ }\mu\text{m}$) Al_2O_3 scales formed. After oxidation, the specimens were sectioned, metallographically polished, and examined. An appropriate section of adherent scale was located (much of the scale was lost by spallation), a matrix of indentation positions covering both metal and oxide was then selected, and an MPM run was initiated. A typical indentation array is shown in Fig. 2.3.1-13. The placement of indentations in the solid oxide product was quite difficult due to detachment of the scale and its thinness. Nevertheless, some

Y217225

Fig. 2.3.2-13. Example of a programmed array of indentations in scale and substrate of an oxidized (900°C , 240 h) Fe_3Al .

mechanical properties data for scales on Fe_3Al has now been obtained and the results are shown in Table 2.3.1-1.

Table 2.2.1-1 Mechanical properties microprobe results from analyses of polished cross sections of scales on oxidized iron aluminides

Material	Hardness (GPa)	Modulus (GPa)
Fe-28Al (Fe_3Al)	24 ± 3	331 ± 18
Fe-36Al (FeAl)	29 ± 2	261 ± 35
Al_2O_3	28 ± 5	
Al_2O_3 (sapphire)	33 ± 2	
Al_2O_3 (literature)	20	400
Fe_2O_3 (literature)	9	220

A key issue in predicting the cracking and spallation of oxide scales is whether the mechanical properties can be gotten from measurements of bulk oxides.²⁵ In order to address this question, and to validate the experimental methods, we are in the process of generating data on bulk oxides using the same MPM. Some very preliminary data on bulk specimens are also shown in Table 2.3.1-1 to facilitate comparison with the scale results. Bulk values from the literature²⁵ are also included. The agreement between the MPM hardness values for bulk oxides and scales is good, particularly in view of (1) the normal variation in the hardness of alumina arising from different microstructures and methods of preparation and (2) the possibility that the scale on Fe_3Al should be expected to have a somewhat lower hardness if some iron oxide is incorporated in it. (As shown in Table 2.3.1-1, Fe_2O_3 has a significantly lower hardness.)

Previous MPM work with chromia-rich scales formed on stainless steel showed excellent agreement between the measured elastic moduli and the literature value for Cr_2O_3 .^{28,29} Referring to Table 2.3.1-1, this is not the case for the alumina scales (although the discrepancy is relatively not great). MPM moduli values for bulk Al_2O_3 are not reported due to problems with the analysis of this property as a function of indenter displacement.

The data is currently being reevaluated using a different approach. Therefore, no definite conclusion regarding the acceptability of using bulk oxide modulus values for prediction of scale behavior can be made at the present time.

During the next reporting period, the mechanical properties task will be focused on (1) methodology development for accurate determination of the hardness and elastic modulus for both bulk oxides and their corresponding scales and (2) determination of the relative changes in these scale properties as a function of the concentration of alloying additions (particularly chromium) to Fe_3Al . This latter work will represent the first step in relating the mechanical properties of scales to compositional modifications of iron aluminides.

2.4 TECHNOLOGY ASSESSMENT AND TECHNOLOGY TRANSFER

2.4.1 Coal Conversion and Utilization Plant Support Services - J. R. Keiser

Support services are being provided to the Advanced Coal Liquefaction Research and Development Facility at Wilsonville, Alabama, whenever requested.

In June 1989, the Wilsonville T102 vacuum tower ceased to operate properly because of suspected corrosion/erosion damage to the trays. An examination was conducted on a component from this tower, a tunnel tray cover from tray 3. Samples for metallographic examination were prepared and examined, and an electron microprobe examination was also performed.

Analysis determined the material was a nominally 12% Cr iron-base alloy, probably type 410 stainless steel. Extensive wall thinning occurred for the portion of the tray cover continuously submerged in liquid, and perforations were formed on horizontal surfaces where splashed or condensed material could collect. The presence of a surface scale and the profile of the thinned surface indicated corrosion rather than erosion was the major cause for the material loss. Electron microprobe analysis of the scale revealed it was composed of oxides and sulfides of chromium, iron, and nickel. The distribution of nickel and sulfur suggests nickel sulfide was present in the scale. Chromium and iron are the major components of type 410 stainless steel, but the nickel was likely from an external source since it was only present at a concentration of 0.3% in the steel. Rapid corrosion of the tunnel tray cover was probably the result of increased activity of sulfidizing compounds or an increase in the operating temperature.

2.5 REFERENCES

1. C. H. Hsueh, P. R. Becher, and P. Angelini, "Effects of Interfacial Films on Thermal Stresses in Whisker-Reinforced Ceramics," *J. Am. Ceram. Soc.* 71(11), 929-33 (1988).
2. B. Z. Egan, *Using Inorganic Membranes to Separate Gases: R&D Status Review*, ORNL/TM-11345, Oak Ridge Natl. Lab., Oak Ridge, Tenn., 1989.

3. J. H. DeVan, "Development of Surface Treatments and Alloy Modifications for Corrosion-Resistant Oxide Scales," pp. 299-310 in *Proceedings of the Fourth Annual Conference on Fossil Energy Materials*, ORNL/FMP-90/1, Oak Ridge Natl. Lab., Oak Ridge, Tenn., August 1990.
4. R. A. Perkins, D. L. Marsh, and A. M. Sarosiek, *Downtime Corrosion in Syngas Coolers of Entrained Slagging Gasifiers*, EPRI AP-5966, Lockheed Missiles & Space Company, Inc., September 1988.
5. R. W. Swindeman et al., *Evaluation of Advanced Austenitic Alloys Relative to Alloy Design Criteria for Steam Service, Part 1, Lean Stainless Steels*, ORNL-6629/P1, Oak Ridge Natl. Lab., Oak Ridge, Tenn., May 1990.
6. L. N. Rubow, *Technical and Economic Evaluation of Ten high Temperature, High Pressure Particulate Cleanup Systems for Pressurized Fluidized Bed Combustion*, DOE/MC/19196-1654, Morgantown Energy Technology Center, Morgantown, W.Va., October 1984.
7. NCB (IEA Grimethorpe) Ltd., *Design of the Facility as of March 1984*, GEF/U/84/22, March 1985.
8. T. E. Lippert, et al., *Performance Evaluation of a Ceramic Cross-Flow Filter on a Bench-Scale Coal Gasifier Volume II*, DOE/MC/21338-2749, Vol.2, Morgantown Energy Technology Center, Morgantown, W.Va., September 1989.
9. R. H. Mallett and R. G. Fasiczka, *Design, Thermal and Mechanical Analysis of a Tubesheet Support for a Hot Gas Cleanup Vessel*, SEAC-TR-576, Swanson Engineering Asso. Corp., McMurray, Pa., January 1990.
10. R. W. Swindeman, R. R. Judkins, and R. H. Mallett, "Identification of Materials for Hot-Gas Filter Tubesheets," pp. 179-84 in *Proceedings of the Seventh Annual Coal-Fueled Heat Engines and Gas Stream Cleanup Systems Contractors Review Meeting*, DOE/METC-90/6110, Morgantown Energy Technology Center, Morgantown, W. Va., March 1990.
11. R. H. Mallett, *Elevated Temperature Structural Design Specification for a Hot Flue Gas Tubesheet*, SEAC-TR-591, Swanson Engineering Assoc. Corp., McMurray, Pa., July 1990.
12. J. M. Corum, et al., *Interim Guidelines for the Detailed Inelastic Analysis of High-Temperature Reactor System Components*, ORNL-5014, Oak Ridge Natl. Lab., Oak Ridge, Tenn., December 1974.
13. R. H. Mallett, *Illustration of Basic Response from the RA333 Materials Behavior Model*, SEAC-TR-595, Swanson Engineering Assoc. Corp., McMurray, Pa., August 1990.
14. R. H. Mallett, *Detailed Structural Evaluation of A Tubesheet for a PFBC Hot Gas Cleanup Vessel*, SEAC-TR-599, Swanson Engineering Assoc. Corp., McMurray, Pa., September, 1990.

15. M. Rao., J. R. Keiser, and D. F. Wilson, "A Study of the Early Stages of Erosion of 1100 Aluminum Using a Mechanical Properties Microprobe," *Scr. Metall.* 23, 1475-80 (1989).
16. M. Rao, J. R. Keiser, and D. F. Wilson, "Subsurface Hardening and Flow of Aluminum During the Incubation Period of Solid Particle Erosion," to be published in the Proceedings of the 4th Berkeley Conference on Corrosion-Erosion-Wear of Materials at Elevated Temperatures, Lawrence Berkeley Laboratories, Berkeley, Calif., January 31-February 2, 1990, National Association of Corrosion Engineers, Houston, Tex.
17. T. Christman and P. G. Shewmon, "Adiabatic Shear Localization and Erosion of Strong Aluminum Alloys," *Wear* 54, 145-55 (1979).
18. A. V. Levy and B. -Q. Wang, "Erosion-Corrosion of Protective Scales on Alloy Steels," *Surf. Coat. Technol.* 33, 285-99 (1987).
19. A. V. Levy and B. -Q. Wang, "The Effect of Test Conditions on the Erosion-Corrosion of Alternate Low Alloy Steel Tubing Alloys," Corrosion 88, Paper No. 147.
20. B. -Q. Wang, G. -Q. Geng, A. V. Levy and W. Mack, "The Erosion-Corrosion of Additional Silicon Low Alloy Steels," Corrosion 90, Paper No. 293.
21. H. E. Evans, *Mater. Sci. Eng.* A120, 139-46 (1989).
22. F. H. Stott, *Mater. Sci. Technol.* 4, 431-38 (1988).
23. M. Schütze, *Mater. Sci. Technol.* 4, 407-14 (1988).
24. M. Schütze, *Mater. Sci. Eng.* A121, 563-69 (1989).
25. J. Robertson and M. I. Manning, *Mater. Sci. Technol.* 6, 81-91 (1990).
26. P. Hancock Nix and J. R. Nicholls, *Mater. Sci. Technol.* 4, 398-406 (1988).
27. W. D. Nix, *Metall. Trans. A* 20A, 2217-45 (1989).
28. P. F. Tortorelli, J. R. Keiser, K. R. Willson, and W. C. Oliver, "Effects of Reactive Elements on Oxide Scale Deformation and Cracking Based on Submicron Indentation Testing," to be published in *Microscopy of Oxidation*, ed. M. J. Bennett and G. W. Lorimer, The Institute of Metals, London, United Kingdom, 1990.
29. P. F. Tortorelli, J. R. Keiser, K. R. Willson, And W. C. Oliver, "Initial Determination of the Micromechanical Properties of Oxide Scales," pp. 463-74 in *Proceedings of the 4th Annual Conference Fossil Energy Materials*, ORNL/FMP-90/1, Oak Ridge Natl. Lab., Oak Ridge, Tenn., R. R. Judkins and D. N. Braski (comp.), August 1990.

3. ENVIRONMENTAL ANALYSIS AND INFORMATION SYSTEMS

C. R. Boston

3.1 ENVIRONMENTAL SUPPORT TO THE CLEAN COAL PROGRAM - R. L. Miller

Activities included assistance to the DOE Office of Clean Coal Technology by initiating work on issue papers discussing environmental topics related to the Clean Coal Program, particularly the effects of commercial deployment of clean coal technologies on those topic areas. Topics of the first three papers are acid deposition, global climate change, and solid waste. A draft of the first paper discussing acid deposition concluded that reductions in sulfur dioxide (SO₂) emissions associated with the widespread commercialization of clean coal technologies should reduce sulfur deposition (the predominant form of acid deposition), especially in the northeastern U.S. and southeastern Canada.

Other work during this six-month period focused on the preparation of two Environmental Assessments (EA's) for demonstration projects selected by DOE in the first and second solicitations of the Clean Coal Program, respectively: Western Energy's Advanced Coal Conversion project at the Rosebud Mine in Rosebud County, Montana, and Combustion Engineering's Integrated Gasification Combined Cycle project at City Water, Light and Power's Lakeside Generating Station in Springfield, Illinois. The EA's are being prepared for the Pittsburgh and Morgantown Energy Technology Centers (PETC and METC), respectively. Both EA's are expected to support documents which conclude that no significant environmental impacts will result from the projects.

The Advanced Coal Conversion project will use a technology that results in an improved fuel by enhancing the thermal value and environmental acceptability of subbituminous coals and lignite. The total potential air emissions from the project are expected to be extremely small in comparison with existing emissions from nearby mining and power generating facilities. The project is designed as a zero discharge facility with no liquid effluents being discharged to the

environment. The project would have negligible effects on terrestrial and aquatic ecology; land use, solid waste, and socioeconomic effects are expected to be minor. Successful future commercial application of the technology would result in reduced atmospheric emissions in regions where the improved quality coal product is burned. Economic benefits, such as lower costs to utilities that use the improved fuel, would also be realized because the need for retrofit pollution control equipment may be reduced or eliminated.

The Integrated Gasification Combined Cycle project involves coupling an existing steam turbine generator with a new coal gasifier and gas turbine to generate electricity, while capturing 95% of the coal's sulfur and producing elemental sulfur as a salable byproduct. Estimated air emissions of sulfur dioxide (SO_2), nitrogen oxides (NO_x), and particulate matter from the project are expected to be small in comparison with existing emissions. Liquid effluents from the project would be discharged from existing permitted outfalls or the municipal wastewater treatment facility. The volume of treated wastewaters discharged should increase, but water quality changes would be restricted to a small area. Impacts to terrestrial and aquatic ecology are expected to be minor, and effects of the project on off-site groundwater and the local economy will be negligible.

Work also has begun for PETC on the preparation of an Environmental Impact Statement (EIS) for the Healy Clean Coal project proposed by the Alaska Industrial Development and Export Authority for Healy, Alaska near Denali National Park. The project is a new 50 megawatt coal-fired power generating facility that is proposed to be collocated with an existing 25 megawatt conventional pulverized-coal unit owned and operated by Golden Valley Electric Association. The new facility will feature integration of advanced combustion and flue gas cleanup technologies to reduce emissions of SO_2 and NO_x . Work during this six-month period included defining information and data needs for the project and preparing a Notice of Intent for the Federal Register that announces the intent to prepare an EIS.

Additional activities included reviews of Environmental Information Volumes and Environmental Monitoring Plans prepared by the

industrial applicants for Clean Coal projects. The final Environmental Information Volumes are used by ORNL as a resource in preparing environmental documentation such as EA's or EIS's for the projects.

4. COAL CONVERSION DEVELOPMENT

C. D. Scott

Coal conversion research has continued on the biological solubilization of coal using intact microorganisms or isolated enzymes. Experiments are continuing on techniques for enhancing the solubility of enzymes in organic media. Preliminary study has established the feasibility of using these biocatalysts in coal cleaning as well. Research associated with mild gasification product characterization has shown mild gasification to be capable of producing relatively light liquids that may be suitable for engine fuel and char that could be suitable for boiler fuel or other purposes.

4.1 BIOLOGICAL COAL CONVERSION - C. D. Scott, B. D. Faison, J. E. Thompson, C. A. Woodward, and S. N. Lewis

This program has examined the feasibility of using biological catalysts for the conversion of coal to useful liquid fuels. Biological reagents potentially useful in this application include intact microorganisms in pure or mixed culture and isolated enzymes. These biocatalysts are employed in aqueous or organic media which would support the formation of solubilization products. There is particular interest in reduced (nonoxidized) products.

Two approaches to biological coal conversion are under consideration, namely (1) direct anaerobic microbial conversion to products such as ethanol and other oxychemicals, and (2) direct anaerobic enzymatic solubilization. The efforts during this period have reflected our continued emphasis on these tasks, including the demonstration of alcohol production by microbial cultures capable of anaerobic interactions with coal and the further investigation of anaerobic enzyme solubilization of coal in organic solvents. We will also present results of a preliminary investigation into the use of biological catalysts for the removal of organically bound heteroatoms (such as sulfur or nitrogen) from the solubilized coal product.

4.1.1 Background

A comprehensive rationale has been previously established for the approaches to be used in the research for the two tasks included in this program. A summary is included here for completeness.

4.1.1.1 Anaerobic Microbial Coal Conversion

This novel approach to biological coal conversion requires the solubilization of coal through microbial activity in the absence of oxygen and under an inert or reducing atmosphere. The principal substrate for this work will be native subbituminous and/or bituminous coals.

The hypothesized product of an anaerobic microbial coal conversion process would be a minimally oxidized material which may be enriched in low-molecular-weight aromatic and aliphatic acids, alcohols, and ketones. These constituents may be formed by direct solubilization or by further metabolism of the products of solubilization. These microbial conversions will initially be carried out in aqueous culture media, although partially or wholly nonaqueous systems will ultimately be considered.

4.1.1.2 Anaerobic Enzymatic Solubilization of Coal

The anaerobic enzymatic process will require the addition of hydrogen to the coal matrix and the probable removal of some oxygen and other heteroatoms. One can envision enzymes that can transfer the gaseous reagent (H_2),

or utilize a hydrogen donor such as sodium dithionite or even other enzymes such as reduced cytochrome C that can serve as electron carriers,

Effective hydrogenase will likely be isolated from microorganisms such as *Proteus vulgaris*, *Desulfovibrio desulfuricans*, and *Chromatium*, or perhaps some of the more recently isolated deep-sea thermophiles.

It may be desirable to utilize a less polar, organic solvent instead of water as the coal solubilization agent since this would also allow easy removal of nonpolar products. Most enzymes are sparingly soluble in organic liquids, but in some cases they may be chemically modified to enhance the solubility. This will have to be done in a way that did not significantly affect the enzyme activity.

4.1.1.3 Removal of Heteroatoms from Solubilized Coal

Coals are known to contain covalently bound heteroatoms such as sulfur and nitrogen. Coal conversion products, whether generated biologically or abiotically, also contain these contaminants. Removal of these heteroatoms is essential to improving product quality. A preliminary investigation supported by discretionary funds is under way to assess the ability of microorganisms to remove organic sulfur or nitrogen from soluble coal-derived materials. Substrates for this work will include compounds representing coal substructures that are soluble in either aqueous or nonaqueous media. The former will be representative of products from microbial coal solubilization in vivo; the latter, representative of products resulting from microbial, enzymatic, or thermochemical coal conversion in vitro.

The goal of this work will be the removal of sulfur or nitrogen from heteroatomic compounds without decreasing the product's fuel value. Efforts will be made to isolate microbial enzymes useful in the cleavage of carbon-sulfur or carbon-nitrogen bonds to yield reduced organic products plus inorganic ions. These enzymes may ultimately be used in vitro within organic solvents. Techniques developed for anaerobic enzymatic coal conversion may be relevant in the latter task.

4.1.2 Results

4.1.2.1 Anaerobic Microbial Coal Conversion

Efforts during this period have focused on the continued testing of *Candida* sp. ML13 (a coal solubilizing organism) and mixed bacterial cultures (organisms associated with Argonne premium coal samples or various environmental isolates) for their ability to catalyze anaerobic transformations of coal.

4.1.2.1.1 *Candida*. Preliminary testing had indicated that this organism produces ethanol from native (unwashed) lignite. Subsequent testing was designed to assess its activity against higher-ranked coals and to determine whether the ethanol is generated from the coal polymer or from leachable material.

Cultures of *Candida* have been incubated with coal, washed coal, or coal leachate for 78 d in the presence or absence of glucose. (Glucose, an easily metabolizable sugar, was added to one set of cultures to promote anaerobic co-metabolism of the coal substrate.) Lignite, subbituminous, and bituminous coals were tested.

Cultures containing glucose produced CO₂, ethanol, and/or acetic acid from all substrates (Table 4.1). Ethanol formation was inhibited in the presence of all coals tested. This result suggests that both leachable and nonleachable coal components are toxic to ethanologenic metabolism. However, more ethanol was produced in cultures containing lignite or lignite-derived material than in those containing subbituminous or bituminous substrates. This suggests that lignite components are less toxic than those from higher-ranked coals (but see below). Alternatively, lignite components may serve as substrates for ethanol formation. Cultures lacking glucose were indeed active against native (unwashed) lignite, but produced only minimal amounts of ethanol (45 mg/L) and acetic acid (12 mg/L). No activity against higher-ranked coals or coal components was observed.

Results presented here contrast with those obtained after a 14-d incubation in which more ethanol was formed from the higher-rank coals than from lignite. Those younger cultures (with the exception of those containing lignite) also produced substantially more ethanol than did the control. Fractions of the higher-rank coal that are amenable to microbial degradation thus appear to be rapidly exhausted. The basis for the apparent high toxicity of lignite fractions to young cultures is not known.

Table 4.1. Conversion of coal and coal-derived substances by *Candida* in the presence of 1% glucose

Substrate	Products (mg/L)		
	CO ₂	Ethanol	Acetate
Control ^a	5.5	1,519	807
Lignite			
Native	29.6	1,056	373
Washed	59.2	705	1,091
Leachate	59.2	651	996
Subbituminous			
Native	trace	98	1,020
Washed	trace	0	39
Leachate	11.1	266	1,714
Bituminous ^b			
Native	5.5	70	1,152
Washed	0	0	41

^aCultures contained 1% glucose only.^bLeachate not tested.

4.1.2.1.2 Environmental Isolates. Testing of environmental isolates has continued, with particular emphasis on determining product composition.

Samples of Argonne premium coals (including lignite, subbituminous, and bituminous coals) have been incubated with medium containing 1% glucose for 77 d. This regimen was designed as a preliminary screen for degradative activity and product range; glucose was added to promote biomass formation. Products formed under these conditions included methane and various alcohols in addition to those compounds listed above (Table 4.2). It is not known whether these products were formed from glucose or from coal itself.

Table 4.2. Product formation from glucose and coal by cultures associated with Argonne premium coal

Culture origin	Products (mg/mL)			
	CH ₄	CO ₂	Ethanol	Acetate
Lignite ^a	4.0	0	11	2,707
Subbituminous ^a	31.8	37.0	0	2,113
Bituminous ^b	59.6	111.0	0	2,921

^aTrace amounts, isopropanol.

^bTrace amounts, butanol.

Microbial consortia (isolated from environmental samples as described previously) were incubated in medium containing subbituminous coal and 1% benzoate for 82 d. This regimen was designed to enhance cultures' ability to degrade aromatic substrates derived from coal. Products formed under these conditions included methane plus acetate and butanol, methane plus butanol, or methane plus CO₂. Methane was always the major product, and in no case was ethanol formed. These findings suggest that cultures are active against aromatic substrates, but that methods to suppress methanogenesis will be needed in order to enhance alcohol formation.

4.1.2.1.3 Characterization of Microbial Consortia. Subsequent experiments focused on the cultivation and study of the mixed cultures in isolation, that is, after their separation from the coal substrates. The cultures were designated L-1 (i.e., of lignite origin), S-1 (i.e., of subbituminous coal origin), and B-1 (i.e., of bituminous coal origin).

A series of experiments were carried out to determine the substrate specificity of the coal-derived microbial isolates. The three microbial consortia were grown in enrichment culture in media containing 1% glucose and then subcultured into 1% solutions of either sodium acetate or sodium benzoate as the sole carbon source. These tests were carried out anaerobically, under nitrogen, at ambient temperature for a total of 42 days. The cultures were also examined microscopically after

7 days in order to establish a tentative characterization by Gram-staining reactions.

The L-1 culture grown in either acetate or benzoate contained Gram-positive nonsporulating rods, Gram-negative rods, and Gram-negative cocci. These organisms were tentatively identified as methanogens (probably *Methanobacterium* and *Methanococcus* spp.), which exhibit Gram variability. However, other species of the family *Enterobacteriaceae*, which are known to produce a variety of acids from organic substrates, may be present as well.

The S-1 culture grown in either acetate or benzoate contained plump Gram-positive and Gram-negative rods, some of which contained spores. Nonsporulating organisms were tentatively identified as members of the family *Bacillaceae* which includes the genera *Clostridium*, *Bacillus*, *Sporolactobacillus*, and *Desulfotomaculum*. Members of these genera are known to produce acids (primarily acetate) and sometimes alcohols (such as butanol) from organic substrates.

The B-1 culture grown in acetate contained Gram-negative rods and Gram-positive rods with spores (tentatively identified as methanogens and bacilli, respectively). However, bituminous coal cultures grown in benzoate contained Gram-negative rods of irregular morphology (tentatively identified as members of the *Propionibacteriaceae* family), plus Gram-negative rods and cocci (probably methanogens). The propionic acid bacteria tend to produce mixtures of organic acids such as propionate and acetate but often include butyrate, formate, lactate, and other monocarboxylic acids. The differences between microbial populations as a function of carbon source are not yet understood.

These tentative identifications are consistent with results we have reported previously that indicated production of methane, acetate, and trace amounts of alcohol by cultures containing glucose plus coal.

4.1.2.1.4 Growth and Product Formation by Microbial Consortia.

Cultures obtained from lignite, subbituminous, and bituminous coals exhibited differing abilities to grow on acetate and benzoate (Table 4.3). The L-1, S-1, and B-1 cultures grew reasonably well on

Table 4.3. Growth of microbial cultures isolated from
Argonne premium coal sample

	Culture Age (d)	Growth (absorbance at 660 nm)	
		Acetate	Benzoate
Lignite culture (L-1)	6	0.015	0.030
	7	0.040	0.045
	14	0.040	0.040
	29 ^a	0.040	0.040
Subbituminous culture (S-1)	6	0.290	0.045
	7	0.360	0.080
	14	0.410	0.050
	29 ^b	0.330	0.070
	42	0.340	0.080
Bituminous culture (B-1)	6	0.280	0.030
	7	0.260	0.040
	14	0.340	0.040
	29 ^b	0.220	0.080
	42	0.220	0.080

^aCulture discarded after 29 d.

^bCultures began to clump at 29 d, resulting in an underestimate of cell density.

acetate, but there was little to no growth on benzoate. Acetate cultures appeared to produce copious amounts of gas, as yet unidentified. Benzoate cultures produced CO₂ (but apparently no methane). Acid and alcohol analyses are currently under way.

These preliminary results suggest that cultures obtained from lignite will not form sufficient biomass to be useful in coal conversion. Cultures from subbituminous and bituminous coals may be useful in degrading aliphatic portions of the coal polymer, presumably with formation of liquid products. However, the small but significant amounts of growth on benzoate, in the absence of methane production, demonstrated by cultures obtained from either subbituminous or bituminous coals suggest that these cultures may also be able to degrade aromatic residues within coal. These cultures may be able to grow on solubilized lignite (which is known to be primarily aromatic in nature). However, their activity against aromatic substrates must ultimately be enhanced for there to be extensive coal solubilization.

4.1.2.2 Enzymatic Solubilization of Coal

Reducing enzymes may enhance the dissolution of coal to low-molecular-weight aromatic fragments in an anaerobic environment. Coal contacted with enzymes in an organic medium should generate products that are relatively nonpolar as are the products of conventional thermal/chemical coal liquefaction processes. The general incompatibility of enzymes with organic solvents requires that the enzymes be modified to decrease their effective polarity and increase their solubility in organic solutions. However, chemically modified enzymes must also have usable catalytic activity in the organic. Experiments this quarter have further explored solubilization and activity of enzymes (hydrogenase and cytochrome C) in organic solution. Preliminary experiments have been performed on the effects of enzymes in organics on coal model compounds.

4.1.2.2.1 Chemical Modification of Enzymes. The most effective method of chemical modification of enzymes that enhances their solubilization in organic solvents has to date been the interaction of

enzymes with methoxypolyethylene glycol (PEG₁, available from Sigma Chemical Company) that has been activated with cyanuric chloride. PEG₁ apparently interacts with the free amino acid groups on the protein molecules. The chemical attachment is generally carried out in aqueous buffer at pH 10 at 25°C for 1 h. Thereafter, the pH is adjusted to 8, and the material is dialyzed against buffer to remove unbound PEG₁, then lyophilized and subsequently dissolved in the organic solvent.

Hydrogenase (isolated from *Proteus vulgaris*) and cytochrome C (obtained from Sigma Chemical Company) were modified with PEG₁. Cytochrome C is known to have 20 free amino acid residues per molecule of the protein, while hydrogenases with similar properties are thought to have 80 free amino acid residues for each molecule. Previous tests were carried out with PEG₁ concentrations that were equivalent to 1 mole PEG₁/mole of free amino acid residues.

After the modified enzymes were dissolved in benzene, the organic was evaporated away and the dried protein was redissolved in 0.1 M phosphate buffer at a pH of 7.0. Previously described techniques were then used to determine enzyme activity, which was reported as enzyme activity/mL of the benzene. It has now been shown that the activity of the modified enzymes in benzene increases as the relative PEG₁ concentration increases. Over the range investigated (a molar ratio of 1 to 10), hydrogenase activity continued to increase; however, cytochrome C activity reached a maximum at a molar ratio of 5:1 and thereafter it decreased. Apparently, additional chemical interaction of the PEG₁ affected the active sites in cytochrome.

4.1.2.2.2 Measurement of Activity of Hydrogenase in Organics. In aqueous solution, the activity of hydrogenase can be determined by the benzyl viologen reduction method previously described. This method cannot be applied to hydrogenase in benzene because of the insolubility of benzyl viologen. However, preliminary results have shown that reduced resazurin (a redox indicator dye) produces a pink color (peak absorbance at 600 nm) in aqueous solution and benzene when contacted with dilute solutions of hydrogenase.

In preliminary tests, 0.8 units of activity of PEG₁-modified hydrogenase was dissolved in 1 mL of benzene and then contacted under a H₂ atmosphere with 1 mL of benzene that contained 1 mg of resazurin. The result was a pink solution with a peak absorbance of 0.35 at 588 nm. When 0.07 enzyme units of activity/mL benzene was used, the reduced dye had a peak absorbance of 0.17 at 588 nm. There was no measurable increase in the absorbance at 588 nm when the enzyme was not present. Additional work will be required in order to properly quantitate the hydrogenase activity.

4.1.2.2.3 Model Compound Studies. Two compounds suggested by Dr. M. Faracasiu as models analogous to coal structural components are 1,2-bis(4-pyridyl) ethane and 1,2-bis(4-quinolyl) ethane. Initial tests were carried out at 30°C in which the degradation rate was determined for small quantities of these model compounds dissolved in benzene in the presence of modified cytochrome C or modified hydrogenase. The concentration of the model compounds was determined on a 5890 Hewlett Packard gas chromatograph was a Janel Scientific DB-5 capillary column. It was shown that 4.5 mg/mL of reduced modified cytochrome C in benzene enhanced the degradation of 1,2-bis(4-quinolyl) ethane during a 3-h period. Similarly 0.7 mg/mL of modified hydrogenase in benzene enhanced the degradation of 1,2-bis(4-quinolyl) ethane during a 3-h period. Similarly, 0.7 mg/mL of modified hydrogenase in benzene enhanced the degradation of 1,2-bis(4-pyridyl) ethane over a 2-h period. This indicated that the biological catalysts did interact with the model compounds, but much additional work needs to be carried out to determine the effect of operating parameters.

4.1.2.2.4 Enzyme-Enhanced Coal Solubilization. Although the major emphasis this period was on studying the enzyme process, a few tests were made on enzyme-enhanced solubilization of coal. As before, it was shown that modified hydrogenase dissolved in benzene and operating at 30°C did enhance solubilization of coal. The tests were similar to those previously made in which 10 mL of the benzene-enzyme mixture and 0.1 g of the size-reduced coal sample were placed in a 25-mL shake flask and a hydrogen atmosphere was maintained. The progress of

dissolution was followed by a periodic measurement of the solution absorbance at 270 to 280 nm. With Wyodak subbituminous coal, there was a modest increase in solubilization of 24% over benzene alone when 0.14 units/mL of hydrogenase was used during a 20-h period. When the modified hydrogenase concentration was increased to 0.67 units/mL of benzene, the solubilization of Illinois #6 bituminous coal was enhanced by as much as 8 times over than obtained with benzene alone during an 18-h period. The total solubilization of the coal was still less than 20% on a dry, ash-free basis.

4.1.2.3 Removal of Heteroatoms from Solubilized Coal

Efforts during this period have been supported by discretionary funds but the results are related to this program so they are included in this report. The work was focused on the evaluation of coal solubilizing organisms as potential catalysts for heteroatom removal from coal-derived material. The specific goal was the demonstration of activity against organically bound sulfur. A variety of hydrophobic coal substructure compounds have been used in this work.

Sulfur-removing experiments were conducted with *Paecilomyces* sp. TLi, a fungus isolated from and known to interact with low-rank coals. Cultures were grown in an inorganic salts medium containing trace (micromolar) levels of sulfur and to which organic sulfur-containing compounds had been added at 2 mM final concentration. Test compounds for this work were dibenzothiophene (DBT, a sulfur heterocycle), ethyl phenyl sulfide, phenyl sulfide, benzyl sulfide, thianthrene, phenyl disulfide, and benzyl disulfide. Cultures were incubated for 10 d and methylene chloride extracts of the broth were analyzed by gas and/or thin-layer chromatography.

Cultures produced oxidized, oxygenated products from DBT. The resulting products of microbial action, including DBT sulfoxide or sulfone plus *o,o'*-biphenol, suggest a specific attack at the sulfur atom. This degradation pathway is considered desirable in that it does not affect the carbon content of the substrate. However, the possible involvement of a parallel, ring cleavage pathway was not ruled out, nor was the ultimate fate of the desulfurization product determined.

Organic sulfides were in some cases shown to be degraded to more oxidized products (i.e., sulfones). Other nonoxygenative reactions occurred as well. For example, phenyl sulfide yielded the corresponding sulfone, plus biphenyl, dibenzothiophene, and phenyl disulfide. Benzyl sulfide produced an even greater array of products (Fig. 4.1). Organic disulfides were apparently cleaved with the formation of thiols.

The variety of products formed suggests the involvement of free-radical mechanisms, including condensations and rearrangements. This activity is consistent with the involvement of an extracellular peroxidase of a type analogous to that used for anaerobic enzymatic coal conversion.

4.1.3 Future Work

Future microbiological studies will focus on adapting the Argonne subbituminous and bituminous cultures to growth on aromatic substrates, without compromising their ability to degrade aliphatic substrates, in order to enhance their total activity toward coal. These cultures will then be manipulated in order to channel metabolic flux toward alcohol production.

Work will continue on the enhancement of solubilization of reducing enzymes in organic solvents, primarily benzene. Further increases in PEG₁ interactions will be tested and the stability of the enzyme at higher temperature will be established with a more definitive assay technique. The assay of hydrogenase activity in an organic medium utilizing reducible dyes will continue to be studied. The reduction of model compounds will continue to be of primary importance as will the enhanced solubilization of bituminous coal.

Efforts will be made to isolate from *Paecilomyces* an enzyme involved in desulfurization activity. Factors controlling the relative yields of oxygenated and nonoxygenated products will be determined. *Paecilomyces'* ability to remove nitrogen from coal substructure compounds will be tested as well.

Benzyl Sulfide
(substrate)

Products:

R = alkyl

Fig. 4.1. Products formed from benzyl sulfide by *Paecilomyces*.

4.2 MILD GASIFICATION PRODUCT CHARACTERIZATION - R. L. Graves

4.2.1 Background

Mild gasification of coal has been shown to be capable of producing relatively light liquids, possibly suitable as an engine fuel, and char that may be suitable for boiler fuel or other purposes. Process conditions greatly influence the product quality, and in particular, liquid product quality suffers with increasing yield. In this investigation, liquid and char products are being characterized such that their basic properties can be related back to processing conditions, coal type, etc. An important part of the characterization includes evaluating the combustion properties of selected liquids and char in addition to more traditional laboratory analyses.

4.2.2 Status Summary

During this reporting period, a coal liquid sample from Western Research Institute (WRI) and pitch samples from AMAX were studied. In a somewhat new part of the activity, we attempted to improve the usefulness of the coal liquids as diesel fuel by adding cosolvents to improve the miscibility of the coal derivatives in diesel fuel.

4.2.3 Liquid Product Diesel Ignition Quality

Typical mild-gasification conditions yield substantial fractions of liquids (Fig. 4.2) which distill with, and are projected to replace, standard middle distillates. This project has been concerned with assessing current mild gasification middle distillates, neat and in several different fuel blends, as fuels for small diesel engines. Although optimizing a variety of fuel properties, e.g., viscosity, energy density, or reactivity, is important in developing a viable fuel, the first concern is estimation of ignition delay in normal combustion. Cetane rating is a measure of this property. Because of the growing concern about the ability of CFR engine cetane measurements to adequately reflect ignition performance of alternative fuels in conventional engines, performance in a Deutz F1L-511W single-cylinder engine was used to measure ignition delay. This dynamometer-mounted, indirect-injection diesel engine has 0.825 liter displacement and 19:1

ORNL-DWG 90M-2935A FED/R

Fig. 4.2. Typical mild-gasification conditions yield liquids with substantial fraction in diesel fuel range. Simulated distillation via GC.

compression ratio. Cetane ranking was extrapolated from the ignition delays relative to those of reference fuels. This procedure has been described in detail elsewhere.¹

Current and previous experience indicates that the ignition qualities of neat coal liquids are insufficient to permit engine operation. A blending system used with high-alcohol diesel fuels was adapted for these tests. Cosolvent fuels blends contained 40% each diesel fuel and coal liquid and 20% of a cosolvent known to improve the performance and phase stability of high alcohol diesel fuels. Fuel blends containing 40% coal liquid and 60% diesel fuel were also examined to determine what effect, if any, the surfactants would have on ignition quality. The coal liquids evaluated included a Western Research Institute 0 to 420°F distillate, the corresponding 420 to 720°F distillate, and a Coal Technology Corporation (UCC2) production run liquid. Diesel fuel - coal liquid blends showed accumulation of a third phase after several hours of storage. Fuels containing cosolvents remained clear, single phase blends for several days. Elemental analyses of the WRI samples are provided in Table 4.4.

Table 4.4. Analysis of liquid fractions

Constituent	Weight percent		
	WRI ^a IBF-420°F	WRI ^a 420-720°F	CTC (UCC2)
Carbon	78.1	81.1	83.7
Hydrogen	8.5	9.2	9.3
Nitrogen	0.3	0.9	0.7
Sulfur	0.9	0.7	0.4
H/C	1.31	1.36	1.34

^aData provided by WRI.

Performance of 11 coal liquid blends is shown in Fig. 4.3. The use of cosolvents did not significantly improve the performance ratings

Fig. 4.3. Apparent cetane number of coal liquid blends. Cosolvents improved storage stability of blends, but had no effect on ignition quality.

of coal liquids. Although it should be possible to develop effective strategies for improving coal distillate fuel performance, the present blends are, at best, marginally suitable for heavy power generation diesels. These fuels are probably inadequate for use in transport or passenger diesels without significant cetane enhancement.

4.2.4 Pitch Characterization

Commercialization of mild gasification will ultimately depend on the creation of a wide variety of products to provide a marketing situation analogous to that of the petrochemical industry. AMAX has been exploring the production of graphite electrodes for aluminum production as a pitch product. Although early use of the product is expected to be primarily in-house, the commercial use of graphite, particularly in composite materials, is steadily increasing. Development of a controlled precursor system producing high quality, low cost pitches would be a major step toward reaching this target market. This could provide a high profit market for an otherwise poorly profitable distillation cut.

The fundamental consideration in developing a graphite precursor pitch is increasing the concentration of unsubstituted polyaromatics to facilitate the growth of graphite crystal structure. AMAX was interested in decreasing the amount of oxygenates in MG-112, a mild gasification pitch. Bob McCormick of AMAX provided progressively heat treated pitch samples. Initial FTIR examination of MG-112 pitch pressed into KBr pellets provided a very complex, difficult to analyze spectrum. Using a method developed by Petersen,² the pitches were dissolved in tetrahydrofuran. This provided FTIR spectra shown in Fig. 4.4. Heat treatment appears to decrease, but not eliminate, oxygenated compounds in mild gasification pitches. Decreases in ketones with increasing temperature were indicated by peaks at 1660 and 1705 cm^{-1} . As indicated by decreases in peaks around 1730 and 1760 $^{-1}$, free acids were also reduced (but not eliminated). Reductions in bands at 3200 cm^{-1} (-OH groups) and 2800-3200 (alkyl groups) with increasing heat treatment were also observed. These results were confirmed by the elemental analysis shown in Table 4.5.

Fig. 4.4. FTIR spectra of heat-treated mile-gasification pitches.

Because of the commercial utility of the pitch materials, future work on catalytic upgrading is planned.

Table 4.5. Composition of heat-treated mild gasification pitches

Constituent	Heat-treatment temperature ^a		
	300°F	350°F	400°F
Carbon	0.842	0.853	0.870
Hydrogen	0.083	0.079	0.072
Sulfur	0.003	0.003	0.002
Nitrogen	0.005	0.005	0.005
Oxygen	0.061	0.053	0.045
Toluene insolubles	0.172	0.341	0.433

^aWeight basis.

4.3 REFERENCES

1. Graves, R. L., et al., "Mild Gasification Product Characterization," Proc. 9th Gasification and Gas Stream Cleanup Systems Contractors Review Meeting, Vol. II, DOE/METC-89/6107, June 1989.
2. Petersen, J. C. "Quantitative Functional Group Analysis of Asphalts Using Differential Infrared Spectrometry and Selective Chemical Reactions - Theory and Application." Transportation Research Record Paper 1094.

5. FOSSIL FUEL COMBUSTION TECHNOLOGY

R. L. Graves

5.1 TECHNICAL SUPPORT TO PETC USAID COLLABORATIVE COAL PROJECTS - R. P. Krishnan

5.1.1 Objectives

In response to the request from the Pittsburgh Energy Technology Center (PETC), the Oak Ridge National Laboratory (ORNL) is providing technical assistance in the implementation of collaborative coal projects under the U.S. Agency for International Development (USAID)/Government of India (GOI) Phase II, Alternative Energy Resources Development (AERD) Project.

5.1.2 Background

In May 1983, the GOI and the USAID initiated the AERD project with a coal conversion component comprised of six collaborative coal projects:

1. Evaluation of freeboard performance in a fluidized bed combustor (FBC);
2. Scale-up of an atmospheric fluidized bed combustion boiler;
3. Rheology, stability, and combustion of coal-water slurries;
4. Beneficiation of fine coals in dense media cyclones;
5. Hot gas cleanup and separation; and
6. Cold gas cleanup and separation.

The PETC, U.S. Department of Energy (USDOE) under a Participating Agency Service Agreement had the management responsibility for implementing the collaborative coal projects. In the FBC projects, ORNL and Bharat Heavy Electrical Limited (BHEL), Trichy, India, were designated as the lead institutions for the collaborative efforts.

The successful completion of the above coal projects in June 1987 led to a strong interest by the participants in the AERD coal conversion projects to continue the involvement of USAID and the USDOE in the following projects.

5.1.2.1 Development of pollution control strategies for abatement of NO_x and SO_x emissions from coal-fired power plants

Nitrogen and sulfur oxide emissions from fossil-fired power plants are expected to increase significantly with the installation of additional coal-fired power plants in India. The composition and characteristics of Indian coals are different from U.S. coals and this will impact the selection of pollution control strategy. The existing data base in India on NO_x/SO_x emissions from coal-fired power plants is not adequate to quantitatively define the magnitude of the emissions, which is the first step in the evaluation of control options.

The objectives of this project are to establish the necessary data base on NO_x/SO₂ emissions by (1) baseline monitoring in selected power plants in India using the state-of-the-art techniques developed in the U.S.; (2) testing known in-furnace control strategies practiced in the U.S. in selected power plants, in India (3) bench-and pilot-scale testing of Indian coals to quantify NO_x/SO₂ emissions; and (4) simulation and modeling of the combustion and heat-transfer processes in the boiler for NO_x/SO₂ prediction.

The BHEL, Trichy, will carry out the project in India as part of their ongoing research and development on NO_x/SO₂ control from coal-fired power plants. Technical assistance from the U.S. will include identification and procurement of state-of-the-art equipment for NO_x/SO₂ measurement, and training of the BHEL engineers in selected U.S. utilities (Tennessee Valley Authority and others) on NO_x/SO₂ monitoring and control technologies, and participation of U.S. experts in the existing bench-scale/pilot scale testing activities at BHEL and in the base line monitoring of Indian power plants.

5.1.2.2 Slagging combustor development for high-ash indian coals

Indian coals have ash content in the range of 35 to 50% and ash fusion temperature over 1482°C (2700°F). For coals of such high-ash content, it would be advantageous from the operational, reliability, and boiler life considerations if the ash can be successfully rejected as a molten slag rather than be allowed to carry over with the flue gas as in conventional pulverized fuel boilers. The slagging coal combustor has been developed

along these lines and is now in the demonstration stage in the U.S. at a utility site.

Recognizing the potential for this technology in India, the BHEL has an active research and development program under way. A 3.0-MW(t) process development unit has been erected and is in operation at Trichy. However, there are several fundamental and engineering issues that are yet to be resolved with respect to Indian coals (slagging potential, slag rejection - quantity and slag properties, ash carry-over from the combustor, optimum air preheat system, operating flexibility - startup, shutdown, and effect of design parameters on slag recovery and combustor operation, carbon utilization and NO_x/SO_2 emissions) before the successful commercialization of the technology in India.

The objectives of this project are to (1) demonstrate whether the slagging combustor technology is suited for Indian coals, (2) identify the engineering problems associated with the design, operation and scale-up of the combustor, and (3) design modifications needed in the BHEL slagging combustor to conduct long duration test runs on a variety of Indian coals differing in ash content and slagging tendency.

U.S. technical assistance in the design review of the BHEL slagging combustor, screening and selection of Indian coals based on their slagging potential, and on-site participation in the testing and data analysis is envisaged.

5.1.2.3 Characterization of indian coals for combustion and gasification

With the deteriorating quality of coal in India (highly erosive coal) coupled with fuel switching by utilities, there is a critical need to quantify the impact of coal quality on power plant performance. Pilot-scale combustion tests are mandatory to provide boiler performance data on combustion efficiency, fuel ignition characteristics, flame stabilization, slagging, fouling, erosion and corrosion of boiler components, and gaseous and particulate emissions. Pilot-scale tests are also necessary for the full-scale burning in commercial boilers. In India, there is no facility available to conduct screening tests on coal.

The objective of this report is to design, erect and commission a pilot-scale Fuels Evaluation Test Facility (FETF) at BHEL, Trichy, which will serve as a focal point for combustion research in India. The PETC

combustion research division and the ORNL will be the lead U.S. institutions collaborating with BHEL, Trichy in this project.

5.1.2.4 Residual life assessment and life extension of coal-fired power plants

The assessment of remaining life of coal-fired power plant components based on quantitative, nondestructive, real-time measurements of the extent of damage to these components is an area which is actively pursued in most advanced countries where the latest diagnostic tools are available. The methodologies and techniques are the key to a successful remaining life assessment program. In keeping with the need for steady and reliable electric supply, the Ministry of Power, Government of India has recently embarked on a multi-million dollar power plant life assessment and rehabilitation program.

This project will be a collaborative effort, initially between the BHEL and the Electric Power Research Institute (EPRI), in which the diagnostic techniques, design criteria, methodologies, and implementation strategies developed by EPRI for the U.S. utilities will be tested in selected Indian utilities. The highly erosive nature of Indian coals will provide an opportunity to test the engineering correlations for prediction of erosion of boiler and auxiliary components, and possibly extend their range of applicability.

5.1.2.5 Environmental and natural resource analysis of coal cycle

The mining, conversion, and disposal of waste and byproducts from coal utilization have serious environmental repercussions in India. Although there are regulations stipulated for air and water quality pollutants, they are not strictly enforced except in urban areas. This policy is going to change in the near future, and several groups are working in the country on allowable limits, environmental considerations for power plant siting, and impact of air/water/soil quality in the vicinity of coal mines and coal burning facilities. In all these tasks, environmental system models and an environmental data base are vital. Air and water quality data are only now being collected in India, mainly around the large power plants in central India.

The goal of this project is to develop environmental system models for prediction of air and water quality near coal-based power plants. The present data base will only permit development of the overall structure of the model and the process/environmental data needed as inputs for the system model. It is expected that the model can be refined as more data becomes available. The methodology and the model inputs and outputs will be established in this project.

The project will be carried out by the Tata Energy Research Institute (TERI), New Delhi. Assistance to TERI will be provided by ORNL, PETC, Environmental Protection Agency in the screening, selection and adaptation of the air/water quality prediction models developed in the U.S. for local conditions.

5.1.3 Status Summary

The major activity during this reporting period was the completion of the equipment specifications and initiation of procurement actions for the equipment at PETC for all the USAID supplied equipment in the four coal projects at BHEL Trichy. In April 1990, the USAID mission, New Delhi requested PETC to put first priority on equipment specifications and the completion of all procurement, including delivery to India by December 31, 1990. Under this redirection, some of the scheduled activities in the four projects had to be postponed.

The engineering design, layout and structural drawings for FETF were completed. A final review of the design is scheduled in November 1990 at PETC with BHEL, ACUREX, Gilbert-Commonwealth and ORNL. After the review, the manufacturing drawings will be released to the BHEL shops. Specifications for the USAID equipment for this project (coal feeders, flame scanners, combustion diagnostic instrumentation, isokinetic gas sampling system, video monitors, heat traced sample lines, air cooled radiator, air velocity meter, heat transfer fluid, air preheater, temperature recorders, pressure transmitters, and data logger) and the BHEL supplied equipment have been completed and procurement action initiated at PETC.

Analyses of the thirty Indian coal samples differing in rank and seam, were completed at PETC. The coals were characterized for proximate,

ultimate, ash composition, ash fusion and sulfur forms. Combustion tests on a lignite and a bituminous coal will be conducted in the PETC fuel evaluation test facility. The tests will provide baseline data on flame stability, carbon burn-out, emissions, slagging and fouling.

In the power plant life assessment project, Dr. R. Viswanathan, EPRI, visited BHEL the Central Power Research Institute (CPRI), the National Thermal Power Corporation (NTPC) and the Power Finance Corporation (PFC) in August 1990. Technical discussions were held with these organizations on power plant remaining life assessment issues. A two-day course on the technical aspects of life assessment was organized at CPRI, Bangalore. This course is offered by EPRI to its member utilities in the U.S. Based on the discussions with the Indian utilities and power agencies, Dr. Viswanathan has recommended to USAID and the GOI to consider a joint power plant life assessment demonstration project at an Indian utility. The demonstration project will provide an opportunity to test and demonstrate the techniques, diagnostic instrumentation and computer codes developed by EPRI for the U.S. utilities.

In August to September 1990, Dr. William C. Peters, USAID Coal Program Manager, PETC and Dr. R. P. Krishnan, ORNL traveled to India to assist the USAID mission, New Delhi, in reviewing the status, identifying the remaining activities and the technical assistance/training requirements to complete the ongoing coal projects at BHEL, Trichy, India. An 18 month time extension beyond the current completion date of December 31, 1990 with additional funding from USAID and BHEL has been recommended to the mission to complete the projects. A detailed report on the individual project status and the remaining activities was submitted to the mission.

Meetings with the CPRI, PFC and the NTPC were held during the visit in August to September 1990 to discuss the joint initiatives in the power sector that are being formulated by the GOI and USAID in the areas of coal-fired power plant remaining life estimation and extension, and the environmental impact of coal-fired power plants.

Assistance was provided by ORNL and PETC to the Indian agencies in developing preliminary proposals to GOI and USAID for a collaborative life extension demonstration project. For details on these activities see ORNL Foreign Trip Report of R. P. Krishnan, ORNL/FTR-3752, October 5, 1990.

During the next reporting period, the coal combustion tests at PETC will be completed. The site activities at FETF, Trichy, will commence and will include the site preparation and fabrication of the combustion and auxiliary systems. A design review of the slagging coal combustor at Trichy by U.S. technical experts, compilation of existing NO_x/SO_x emission data from coal fired power plants in India, and the selection of power plants for baseline monitoring of NO_x/SO_x with U.S. experts are planned.

5.2 SUMMARY

In response to the request from PETC, ORNL is providing technical assistance in the implementation of collaborative coal projects under the USAID/GOI Phase II, AERD Project.

The major activity during this reporting period was the completion of the equipment specifications and initiation of procurement actions for the equipment at PETC for all the USAID supplied equipment in the four coal projects at BHEL, Trichy.

In the power plant life assessment project, Dr. R. Viswanathan, EPRI, visited BHEL, CPRI, NTPC and PFC in August 1990. Technical discussions were held with these organizations on power plant remaining life assessment issues.

APPENDIX. ORGANIZATION CHART FOR THE FOSSIL ENERGY PROGRAM

October 1, 1990

INTERNAL DISTRIBUTION

1-2.	Central Research Library	36.	J. R. Keiser
3.	Document Reference Section	37.	D. G. Kilgore
4-5.	Laboratory Records Department	38.	E. H. Krieg, Jr.
6.	Laboratory Records, ORNL RC	39.	R. P. Krishnan
7.	ORNL Patent Section	40.	W. R. Laing
8-10.	M&C Records Office	41.	D. D. Lee
11.	T. M. Besmann	42.	R. M. Lee
12.	A. Bleier	43.	P. N. Leiby
13.	C. R. Boston	44.	R. A. Lowden
14.	A. C. Buchanan	45.	C. G. McKamey
15.	P. T. Carlson	46.	R. L. Miller
16.	R. R. Chambers	47.	J. E. Mrochek
17.	C. S. Daw	48.	D. E. Reichle
18.	J. H. DeVan	49.	C. D. Scott
19.	B. D. Faison	50.	W. D. Shults
20.	E. C. Fox	51.	S.P.N. Singh
21.	W. Fulkerson	52.	J. H. Stewart, Jr.
22.	E. L. Fuller, Jr.	53.	D. P. Stinton
23.	A. S. Garrett	54.	R. W. Swindeman
24.	R. K. Genung	55.	V. J. Tennery
25.	R. W. Glass	56.	J. F. Thomas
26.	G. M. Goodwin	57.	V. R. Tolbert
27.	R. L. Graves	58.	B. A. Tomkins
28.	C.-H. Ho	59.	D. B. Trauger
29.	D. B. Hunsaker, Jr.	60.	M. Uziel
30-35.	R. R. Judkins		

EXTERNAL DISTRIBUTION

- 61-63. AIR PRODUCTS AND CHEMICALS, P.O. Box 538, Allentown, PA 18105

P. Dyer
J. Slusser
S. C. Weiner

64. ALBERTA RESEARCH COUNCIL, Fuel Sciences Division, Coal
Research Center, 1 Oil Patch Drive, P.O. Box 1310, DeVon,
Alberta, Canada T6G 2C2

S. K. Chakrabartty

- 65-67. ARGONNE NATIONAL LABORATORY, 9700 S. Cass Avenue, Argonne,
IL 60439

W. A. Ellingson
C. D. Livengood
D. K. Schmalzer

68. ATLANTIC RICHFIELD COMPANY, 8840 Iris Court, West Minister,
CO 80020-4454

D. W. Bailey

69. BABCOCK & WILCOX, 1562 Beeson St., Alliance, OH 44601
Contract Research Division

T. I. Johnson

- 70-71. BATTELLE COLUMBUS LABORATORIES, 505 King Ave.,
Columbus OH 43201

R. D. Litt
J. H. Oxley

72. BERGBAU-FORSCHUNG GmbH, Postfach 130140, D-4300 Essen 13,
Federal Republic of Germany

Gunter Faith

73. BETHLEHEM STEEL CORPORATION, Homer Research Laboratories,
Bethlehem, PA 18016

J. M. Chilton

74. BRITISH GAS PLC, Westfield Development Center, Cardenden,
Fife, KY5 OHP, Scotland

J. E. Scott

75. BROOKHAVEN NATIONAL LABORATORY, Department of Applied Science,
Upton, Long Island, NY 11973

T. E. O'Hare

76. CATALYTIC, INC., P.O. Box 239, Wilsonville, AL 35186

J. Howard

77. CHEVRON RESEARCH COMPANY, 576 Standard Avenue,
Richmond, CA 94508

J. H. Shinn

78. CIEMAT (Energetic, Environment and Technological Research
Center), Programa Procesos Mineralurgicos, Avda,
Complutense, 22 Madrid-28040, Spain

G. Morales-Calvo

79. COAL AND SYNFUELS TECHNOLOGY, 1401 Wilson Blvd., Suite 900,
Arlington, VA 22209

P. A. Paquette, Editor

80. COMMISSION OF THE EUROPEAN COMMUNITIES, Petten Establishment,
Postbus 2, 1755 ZG Petten, The Netherlands

M. Van de Voorde

- 81-82. CONSOLIDATION COAL CO., R&D Department, 4000 Brownsville Road,
Library, PA 15129

F. P. Burke
D. G. Nichols

- 83-88. ELECTRIC POWER RESEARCH INSTITUTE, P.O. Box 20412,
3412 Hillview Avenue, Palo Alto, CA 94303

S. B. Alpert	J. Stringer
S. Gehl	R. H. Wolk
D. M. Golden	K. E. Yeager

89. ENERGISTICS CORPORATION, 9210 Route 108, Columbia, MD 21045

Andy Lawrence

90. EXXON RESEARCH AND ENGINEERING COMPANY, Clinton Township,
Route 2 East, Annandale, NJ 08801

M. L. Gorbaty

91. GAS RESEARCH INSTITUTE, 8600 West Bryn Mawr, Chicago, IL 60631

V. L. Hill

92. GENERAL APPLIED SCIENCE LABS, 77 Raynor Ave.,
Ronkonkoma, NY 11779

Martin Novack

93. GENERAL ELECTRIC COMPANY, P.O. Box 8, Schenectady, NY 12301

R. P. Shah

94. ILLINOIS STATE GEOLOGICAL SURVEY, 615 E. Peabody,
Champaign, IL 61820

Mary Krick

95. INTECH, INC., 11316 Roven Drive, Potomac, MD 20854
P. A. Lowe
96. JET PROPULSION LABORATORY, 4800 Oak Grove Drive, Pasadena, CA 91103
R. L. Phen
97. KERNFORSCHUNGSANLAGE JUELICH, Institute for Chemical Technology, Postfach 1913, 5170 Juelich, Germany
Heidrun Barnert-Wiemer
98. KOH SYSTEMS, INC., 164 Rollins Avenue, Rockville, MD 20852
C. W. Di Bella
99. LUMMUS CREST, INC., Engineering Development Center, 1515 Broad Street, Bloomfield, NJ 07003
M. I. Greene
100. MOBILE RESEARCH AND DEVELOPMENT CORPORATION, Engineering Department, P.O. Box 1026, Princeton, NJ 08540
D. F. Palazzo
101. M. L. Myers, 5404 Palmetto Road, Knoxville, TN 37921
- 102-106. NASA LEWIS RESEARCH CENTER, 21000 Brookpark Road
Cleveland, OH 44135
J. A. DiCarlo (M.S. 106-1)
J. P. Gyekenyesi (M.S. 6-1)
H. B. Probst (M.S. 49-1)
J. Shannon (M.S. 49-7)
H. Sliney (M.S. 23-2)
107. NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY, Materials Building, Gaithersburg, MD 20899
S. J. Dapkunas
108. NEW ENERGY DEVELOPMENT ORGANIZATION, Sunshine 60 Bldg., P.O. Box 1151, 1-1, Higashi-Ikebukuro 3-chome, Toshima-Ku, Tokyo, 170, Japan
K. Terunuma

109. NEW ENERGY DEVELOPMENT ORGANIZATION, 1800 K Street, NW,
Suite 924, Washington, DC 20006

T. Yamamoto

110. OAK RIDGE ASSOCIATED UNIVERSITIES, P.O. Box 117, Oak Ridge,
TN 37831

MERT Division Library

111. OGDEN ENVIRONMENTAL SERVICES, INC., P.O. Box 85178, San Diego,
CA 92138-5178

W. S. Rickman

112. PROMON ENGENHARIA S.A., Praia do Flamengo, 154-9 Andar,
22210 Rio de Janeiro, RJ Brazil

Maury Saddy

113. RESEARCH TRIANGLE INSTITUTE, Technical Library,
P.O. Box 12194, Research Triangle Park, NC 27709

R. Whisnant

- 114-115. RISO NATIONAL LABORATORY, P.O. Box 49, DK-400, Roskilde,
Denmark

P. S. Christensen
Aksel Olsen

116. SHELADIA ASSOCIATES, INC., Suite 100, 15825 Shady Grove Road,
Rockville, MD 20850

Leah Reed

117. G. SORELL CONSULTING SERVICES, 49 Brookside Terrace,
North Caldwell, NJ 07006

G. Sorell

118. SRS TECHNOLOGIES, 990 Explorer Blvd. NW, Huntsville, AL 35806

Rodney Bradford

119. STATE ELECTRICITY COMMISSION OF VICTORIA, Howard Street,
Richmond, Victoria, 3121, Australia

Herman Research Laboratory Library

120. SUMMIT TECH, INC., 6551 Loisdale Ct., Springfield, VA 22150

M. R. Schmid

121. TENNESSEE VALLEY AUTHORITY, Chestnut Street, Tower II,
Chattanooga, TN 37401

J. R. Byrd

122. TENNESSEE VALLEY AUTHORITY, Energy Demonstration and
Technology, 2N58A Missionary Ridge Place, Chattanooga, TN
37402-2801

C. M. Huang

123. TEXAS EASTERN TRANSMISSION CORPORATION, P.O. Box 2521,
Houston, TX 77252

D. H. France

124. UNION CARBIDE CORPORATION, Linde Division, P.O. Box 44,
East Park Drive and Woodward Ave., Tonawanda, NY 14150

Harry Cheung

125. UNITED COAL COMPANY, P.O. Box 1280, Bristol, VA 24210

R. A. Wolfe

126. UNITED ENGINEERS AND CONSTRUCTORS, 30 South 17th Street,
P.O. Box 8223, Philadelphia, PA 19101

A. J. Karalis

127. U.S. DEPARTMENT OF TREASURY, 806 15th Street, NW, Suite 410,
Washington, DC 20220

J. Benton

128. U.S. ENVIRONMENTAL PROTECTION AGENCY, Air and Energy Research
Laboratory, Research Triangle Park, NC 27711

T. K. Janes (MD-62B)

129. UNIVERSITE DE METZ, Laboratoire de Chimie Organique, Faculty
des Sciences, Ile du Saulcy 57 Metz, France

Gilbert Kirsch

130. UNIVERSITY OF CHICAGO, Bldg. 201, 9700 S. Cass Avenue,
Argonne, IL 60439

Office of the Vice President for Research

- 131-132. UNIVERSITY OF DELAWARE, Department of Chemical Engineering,
Colburn Laboratory, Newark, DE 19711

W. H. Calkins
G. A. Mills

133. UNIVERSITY OF KENTUCKY, Mechanical Engineering Department,
Lexington, KY 40506-0046

O. J. Hahn

134. THE UNIVERSITY OF OKLAHOMA, Room 107, Carson Engineering
Center, 202 West Boyd, Norman, OK 73019

B. L. Crynes

- 135-136. UNIVERSITY OF PITTSBURGH, 1249 Benedum Hall, Pittsburgh,
PA 15261

I. Wender
Bevier Engineering Library

137. UNIVERSITY OF TENNESSEE SPACE INSTITUTE, Tullahoma, TN 37388

Y.C.L. Wu

138. VEBA OEL, P.O. Box 45, 4650 Gelsenkirchen-Buer, Federal
Republic of Germany

K. Fuhrmann

139. R. E. Vener, 11 Dellcastle Court, Gaithersburg, MD 20879

140. WESTINGHOUSE ELECTRIC CORPORATION, 114 Kenteel Road,
Pittsburgh, PA 15237

D. H. Archer

141. WESTINGHOUSE ELECTRIC CORPORATION, 1310 Beulah Road,
Pittsburgh, PA 15235

D. L. Keairns

142. DEPARTMENT OF ENERGY, Chicago Operations Office,
9800 S. Cass Ave., Argonne, IL 60439

F. Herbaty

- 143-154. DEPARTMENT OF ENERGY, Morgantown Energy Technology Center,
P.O. Box 880, Morgantown, WV 26505

T. F. Bechtel	R. Johnson
W. A. Brown	M. J. Mayfield
D. C. Cicero	W. Miller
M. R. Gbate	J. W. Notestein
J. S. Halow	K. Smith
N. Holcombe	J. S. Wilson

155. DEPARTMENT OF ENERGY, Naval Reactors, NE-60, Crystal City,
Bldg. N.C.-2, Washington, DC 20585

J. Mosquera

- 156-157. DEPARTMENT OF ENERGY, Oak Ridge Operations Office,
P.O. Box 2008, Oak Ridge, TN 37831-6269

Deputy Assistant Manager for Energy Research and
Development
E. E. Hoffman

- 158-179. DEPARTMENT OF ENERGY, Office of Fossil Energy, Washington,
DC 20545

D. J. Beecy - FE-13	H. C. Johnson - FE-13
R. J. Braitsch - FE-13	R. L. Kane - FE-13
P. H. Buhl - FE-22	F. A. Leone - FE-35
J. P. Carr - FE-24	R. C. Porter - FE-10
A. G. Dietz, Jr. - FE-10	J. J. Pyrdol - FE-13
W. Fedarko - FE-22	P. C. Scott - FE-14
K. N. Frye - FE-30	T. B. Simpson - FE-34
H. N. Giles - FE-442	M. I. Singer - FE-30
D. Gray - FE-431	H. E. Thomas - FE-33
A. W. Hemenway - FE-24	G. E. Voelker - FE-23
H. W. Hocheiser - FE-13	G. F. Wheeler - FE-24

- 180-181. DEPARTMENT OF ENERGY, Office of Health and Environmental
Research, Washington, DC 20585

N. F. Barr - ER-72
A. P. Duhamel - ER-74

182. DEPARTMENT OF ENERGY, Office of Health and Environmental
Research, 14 Goshen Ct., Gaithersburg, MD 20879

F. J. Wobber

183-199. DEPARTMENT OF ENERGY, Pittsburgh Energy Technology Center,
P.O. Box 10940, Pittsburgh, PA 15236

S. Akhtar	S. R. Lee
A. L. Baldwin	S. Rogers
B. D. Blaustein	J. A. Ruether
S. W. Chun	T. C. Ruppel
J. L. Hebb	R. Santore
J. D. Hickerson	T. M. Torkos
R. F. Hickey	J. W. Wiggins (3)
J. J. Lacey	

200-209. DEPARTMENT OF ENERGY, Office of Scientific and Technical
Information, P.O. Box 62, Oak Ridge, TN 37831

For distribution by microfiche as shown in
DOE/OSTI-4500, Distribution Categories
UC-122 [Enhanced Oil Recovery (Heavy,
Light)], UC-123 (Oil Shale and Tar Sands),
UC-125 (Liquid Fuels Research), UC-126
(Petroleum Reserves), and UC-132
(Unconventional Gas Recovery).

END

**DATE
FILMED**

2 / 10 / 92