DOE/PC/90258--T1-Vol.1

FINAL REPORT

DOE/PC/90258--T1-Vol.1

DE93 005136

**CHARACTERIZATION & SUPPLY
of
COAL BASED FUELS**

Volume 1 of 2

Final Report & Appendix A (Topical Report)

U.S. DOE Contract No. DE-AC22-86 PC 90258

by

ENERGY INTERNATIONAL
135 William Pitt Way
Pittsburgh, PA 15238

MASTER

June 1992

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

"CHARACTERIZATION AND SUPPLY OF COAL-BASED FUELS"

FINAL REPORT

PERFORMED FOR THE DEPARTMENT OF ENERGY UNDER
PRIME CONTRACT NO. DE-AC22-86PC90258

PERFORMED BY ENERGY INTERNATIONAL, INC.
135 WILLIAM PITT WAY
PITTSBURGH, PA 15238

Submitted June, 1992

JUG 28 1992

DISCLAIMER

This report was prepared in an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

U.S. GOVERNMENT PRINTING OFFICE

ACKNOWLEDGMENT OF PARTICIPATION

Many firms and organizations participated in the accomplishments under this contract, in the forms of technical services and support services. Those who participated to a substantial degree are acknowledged here in alphabetical order:

ABF Freight Systems
Allis Minerals Systems
AMAX Research & Development Center
Carlucci Construction Company
Coal Quality Development Center - EPRI
 (now CQ Inc.)
Commercial Testing & Engineering
Consolidation Coal Company
Dravo Engineering Companies
Energy & Environmental Research Center
 at the University of North Dakota
Jacobson Inc.
Minnesota Custom Processing, Inc.
Otisca Industries, Inc.
OXCE Fuel Company
Particle Reduction Services Company
Penn-Rillton (Division of Whibco)
Virginia Polytechnic Institute and State University
 (also known as Virginia Tech)
Westmoreland Coal Company
Yellow Freight Systems, Inc.

TABLE OF CONTENTS

	<u>Page No.</u>
1.0 EXECUTIVE SUMMARY	1
2.0 INTRODUCTION & BACKGROUND	4
3.0 OBJECTIVES AND SCOPE OF WORK	6
3.1 Contract Objectives	6
3.2 Contract Scope of Work	6
3.3 Task 1 Objectives	6
3.4 Task 2 Objectives	7
3.5 Task 3 Objectives	8
4.0 TASK 1 - ANALYSIS OF FUEL NEEDS	9
4.1 Survey of Combustor Contractor Fuel Needs and Development of Fuel Specifications	9
4.2 Coal Resources and Market Assessment	9
4.3 Selection of Candidate Coals	13
5.0 TASK 2 - CHARACTERIZATION AND FORMULATION OF COAL BASED FUELS	16
5.1 Procurement and Sampling of Candidate Coals	16
5.2 Analysis of Candidate Coals	16
5.3 Washabilities of Candidate Coals	16
5.4 Bench-Scale Flotation Testing	29
5.5 Selection of Baseline Coal	33
5.6 Coal-Water Fuel Development	33
5.6.1 Selection of CWF Manufacturer	33
5.6.2 Slurry Fuel Preparation by AMAX Coal Company . . .	35
5.6.3 Slurry Characterization	37
5.7 Dry Ground Coal Preparation	45
5.8 Availability of Coal Deep Cleaning Services (Procurement Package MN-01-2003)	49
6.0 TASK 3 - FUEL SUPPLY	57
6.1 Coals Used for Fuel Preparation	57
6.2 Deep Cleaning of Candidate Coals	57
6.2.1 Preparation of Deep Cleaned Upper Elkhorn #3 Coal by Dravo	57
6.2.2 Other Cleaning Methods	59
6.3 Preparation and Delivery of Coal-Water Fuel	63
6.4 Preparation and Delivery of Dry Ground Coal Fuel	66
6.5 Quality Control/Quality Assurance Procedures	66
7.0 CONTRACT ACTIVITIES UNDER MODIFICATION #A014	78
8.0 RESULTS AND CONCLUSIONS	84

LIST OF TABLES

	<u>Page No.</u>
4.0-1 . . . Specifications for Solid Fuel	12
4.0-2 . . . Specifications for Coal-Water Fuels	12
4.0-3 . . . Candidate Coals for Residential, Commercial, and Light Industrial Markets	14
4.0-4 . . . Candidate Coals for Slagging Combustors	15
5.0-1 . . . Selected Coals for Residential, Commercial, and Light Industrial Markets	17
5.0-2 . . . Parent Coal Analysis	18
5.0-3 . . . Washabilities of the Upper Elkhorn #1 Coal	20
5.0-4 . . . Washabilities of the Upper Elkhorn #2 Coal	21
5.0-5 . . . Washabilities of the Upper Elkhorn #3 Coal	22
5.0-6 . . . Washabilities of the Lower Elkhorn Coal	23
5.0-7 . . . Coal-Water Fuel Specifications	24
5.0-8 . . . Properties of Coal-Water Slurries Prepared by AMAX Research & Development Center	36
5.0-9 . . . High Shear Viscosities of AMAX Slurry	38
5.0-10 . . . Properties of Reformulated Slurry	42
5.0-11 . . . Dry Ground Coal Specifications	47
5.0-12 . . . (Table omitted intentionally)	48
5.0-13 . . . Analysis of Clean Coals Prepared by Selected Contractors	51
6.0-1 . . . Coals Purchased and Used for Fuel Production	58
6.0-2 . . . Elemental Analysis of Beulah-Zap Lignite Coal before and after Physical and Chemical Cleaning	62
6.0-3 . . . Chemical Deashing of Lignite Coal	64
6.0-4 . . . Analyses of Lignite Coal Samples	65
6.0-5 . . . Coal Bed Abbreviations	68

LIST OF TABLES
(Continued)

	<u>Page No.</u>
6.0-6 . . . Coal or Fuel Form Abbreviations	69
6.0-7 . . . Sample Origin Designation	70
6.0-8 . . . Data Sheet for the Coal Samples	74
6.0-9 . . . Data Sheet for the Slurry Fuels	75
6.0-10 . . . Data Sheet for the Solid Coal Fuels	76
7.0-1 . . . Fuel Specifications	79

LIST OF FIGURES

	<u>Page No.</u>
4.0-1 . . . Fuel Survey and Supply Survey Dry Micronized Coal . .	10
4.0-2 . . . Fuel Survey and Supply Survey Coal-Water Slurries . .	11
5.0-1 . . . Washability Curves of Upper Elkhorn #3 Coal at 1/8 x 0 Mesh	25
5.0-2 . . . Washability Curves of Upper Elkhorn #3 Coal at 28 x 0 Mesh	26
5.0-3 . . . Washability Curves of Upper Elkhorn #3 Coal at 100 x 0 Mesh	27
5.0-4 . . . Washability Curves of Upper Elkhorn #3 Coal at 200 x 0 Mesh	28
5.0-5 . . . Froth Flotation Cleaning of Upper Elkhorn #1	30
5.0-6 . . . Froth Flotation Cleaning of Upper Elkhorn #3	31
5.0-7 . . . Froth Flotation Cleaning of Upper Elkhorn #2	32
5.0-8 . . . Froth Flotation Cleaning of Lower Elkhorn	34
5.0-9 . . . High Shear Viscosity using Burrell Extrusion Tube Rheometer	39
5.0-10 . . . Particle Size Distribution of AMAX Slurry (UE3-217(b)-CWF-G)	40
5.0-11 . . . Particle Size Distribution of OXCE Slurry (UE3-188-CWF-F)	41
5.0-12 . . . Particle Size Distribution of Reformulated AMAX Slurry (UE3-217(c)-CWF-G)	43
5.0-13 . . . Coal Supply Development Center Froth Flotation Circuit	53
5.0-14 . . . Summary of UNDEERC's Coal Cleaning Experiments . . .	54
5.0-15 . . . Otisca "T Process" Circuit Diagram	55
5.0-16 . . . Virginia Tech Microbubble Flotation Column	56
6.0-1 . . . Dravo Pilot Froth Flotation Circuit	60
6.0-2 . . . Sample Identification Scheme	67
6.0-3 . . . Sampling Scheme	71

LIST OF APPENDICES

- A . . . Analysis of Fuel Needs and Selection of Candidate Coals
- B . . . OXCE Fuel Company's Micronized Coal-Water Slurry
Formulation Report
- C . . . OXCE Fuel Company's Standard Grind Slurry Formulation Report
- D . . . Dravo's Flotation Reagent Optimization Report
- E . . . Deliveries of Slurry Fuels to Combustor Contractors
- F . . . Deliveries of Dry Coal Fuels to Combustor Contractors
- G . . . Coal Cleaning Report from Coal Quality Development Center
- H . . . Coal Cleaning Report from Otisca Industries, Ltd.
- I . . . Coal Cleaning Report from the University of North Dakota
Energy and Environmental Research Center
- J . . . Coal Cleaning Report from Virginia Tech
- K . . . Sample Data Sheets
- L . . . Sample Shipment Log
- M . . . Fuels Delivered During the Period May 1990 to August 1991

1.0 EXECUTIVE SUMMARY

The objectives of this project were:

- Develop fuel specifications to serve combustor requirements.
- Select coals having appropriate compositional and quality characteristics as well as an economically attractive reserve base.
- Provide quality assurance for both the parent coals and the fuel forms.
- Deliver premium coal-based fuels to combustor developers as needed for their contract work.
- Establish the capability for combustion test contractors to readily obtain these premium quality test fuels for their future testing needs and for fuel suppliers to have the processing experience to provide reliable quotes and fuels.

Studies and data applicable for fuel markets and coal resource assessments were reviewed and evaluated to provide both guidelines and specifications for premium quality coal-based fuels. The fuels supplied under this contract were provided for testing of advanced combustors being developed under Pittsburgh Energy Technology Center (PETC) sponsorship for use in the residential, commercial and light industrial (RCLI) market sectors. The requirements of the combustor development contractors were surveyed and periodically updated to satisfy the evolving needs based on design and test experience. Available coals were screened and candidate coals were selected for further detailed characterization and preparation for delivery. A team of participants was assembled to provide fuels in both coal-water fuel (CWF) and dry ultrafine coal (DUC) forms.

Information about major U.S. coal fields was correlated with market needs analysis. Coal fields with major reserves of low sulfur coal that could be potentially amenable to premium coal-based fuels specifications were identified. The fuels requirements were focused in terms of market, equipment and resource constraints. With this basis, the coals selected for developmental testing satisfy the most stringent fuel requirements and utilize available current deep-cleaning capabilities.

The primary coal selected as the baseline coal for this supply project is the correlated bed #151 and is designated as the Upper Elkhorn #3 (UE3) coal. This coal has reserves in excess of 13 billion tons in a four state region (KY, VA, WV, TN). It has been shown to be available from existing large scale mining operations and can be readily cleaned to meet the stringent requirements (<1.2% ash - residential, <1.5% ash - commercial and light industrial, <0.8% S for all) for this contract. For this fuel supply contract, EI obtained this coal from the Taggart seam through Westmoreland Coal's Wentz Preparation Plant. In addition to the primary coal, EI identified additional coals suitable to meet other needs of the combustor developers in the program.

Quantities of deep-cleaned coal were prepared in Dravo's froth flotation pilot plant wash circuit and at EPRI's Homer City facilities. Slurries were prepared by OXCE Fuel Company and AMAX R&D Center; micronized and pulverized dry coals by Jacobson, Inc. and Minnesota Custom Processing; and low-rank coals at the University of North Dakota's Energy & Environmental Research Center with assistance from AMAX.

A diversity of fuels were supplied and they fall into the following categories:

<u>Fuel Forms</u>	<u>Coal Types</u>	<u>Users</u>
Micronized CWF	<u>UE3 Baseline Coal <0.8% S</u>	Atlantic Research
Pulverized CWF	Residential <1.2% ash	Avco Research Labs
Micronized DUC	Commer & Light Indust. <1.5% ash	Catholic University
Pulverized DUC	Low Ash WRM 2-3.5% ash	Combustion Engr.
Bulk Coal	Standard Ash WRM 5-7% ash	Energy & Environ. Res.
		MTCI
	<u>Other Coals</u>	Navy Civil Engr. Lab
	PA, OH, WV Slagging	PETC
	Subbituminous	Purdue Mech Engr Dept
	Lignite	SAIC
		Tecogen
		Univ Tenn Space Inst
		Vortec

Individual shipment quantities range from as little as a single drum to as much as:

- 102 tons of bulk coal
- 46 tons of micronized dry coal
- 30,000 gallons of coal water slurry

Of the more than 500 tons of coal fuels supplied under this contract for combustion development testing, some 55 tons were delivered as deeply-cleaned slurry and powder fuel products. Both the total quantity of coal water slurry and the number of individually prepared shipments of slurry exceed the dry powder delivered. Roughly equal quantities of micronized and standard grind slurries were delivered.

At the end of the contracted fuel delivery schedule, it was deemed appropriate to extend the fuel preparation experience base in anticipation of future requirements to support the next phases of combustor development and demonstration. This required addressing both added specifications and qualifying other cleaning technologies and providers to enable these fuels to be more broadly available to future contract needs. To do so involved addressing issues such as ash chemistry, ash fusion temperatures, the need for deep-cleaning, and differences in coal-water fuels prepared by different methods. To support at least a portion of these issues, demonstrations of coal deep-cleaning capabilities were conducted at several different facilities. The ability to clean the UE3 coal to the RCLI standards was demonstrated by heavy media, conventional flotation, microbubble column flotation, agglomeration, and mild acid treatment methods.

Under this contract, the premium quality coal-based fuels needed for the advanced combustor projects sponsored by PETC were supplied and the capabilities to meet this type of need were demonstrated. This does not assure that such fuels will be available to industry for large scale demonstration projects and for commercial applications, but the coals and technologies used are all considered to be representative of those which can be brought to commercialization.

2.0 INTRODUCTION & BACKGROUND

Under the Department of Energy's Advanced Combustor Technology Program, approximately 11 combustor contractors (under 13 contracts) were developing combustion systems (during 1987-1989) for use in residential, commercial, light industrial and industrial retrofit markets. Sufficient quantities of well-characterized, coal-based fuels possessing specific, appropriate specifications are required by the contractors for their developmental test programs. Fuels may be dry pulverized coal or coal liquid fuels. In support of these equipment development efforts, the team of Energy International and Dravo Engineers provided such fuels (under DOE Contract DE-AC22-86PC90258 within the PETC Alternate Energy Program).

Nearly a third of the total energy use in the U.S. is in the residential, commercial, and light industrial sectors. Of this, about half of the energy is supplied by the direct consumption (not including electricity) of conventional oil and gas resources. Thus, there is a significant energy use component for which coal is not currently a viable user option.

For coal to significantly penetrate this important market sector, it must be demonstrated that:

- Premium coal-based fuels can be made, combusted, and used in low maintenance, automatic use systems to which such users are accustomed, i.e., by a direct replacement for conventional fuels and require only simple installation changes.
- Advanced coal fuel combustion systems can effectively combust coal based fuels while meeting economic, environmental, and performance standards.
- Coal fuels, combustion systems and service support are well matched, reliable, cost effective, and are anticipated to be available over the projected lifetime of the installations.

The key to the development of fuel and combustor technologies for future application to the use of premium coal-based fuels in these market sectors is to make representative coal fuels available for developmental testing. Current coal cleaning and processing technologies in early development states offer the promise to meet the market, the performance and the environmental acceptability that are expected to be required. They are not economically competitive now and production facilities are presently limited to experimental and pilot-scale operations which do not offer the economy of scale to reduce costs to the minimum. This is not likely to change with the current plentiful supplies of relatively low cost fuels.

The developmental testing of advanced combustion equipment systems requires fuels for testing; test experience and performance measures are needed to identify cost competitiveness in the market and specific market niches for early commercialization; and, commercial market opportunities are needed to justify and specify the development and installation of advanced fuels facilities for supplying the developmental testing needs.

The capability to produce significant quantities of coal based fuels cannot be supported in the current economic and energy use situation. Once these pieces of experience and information begin to fall into place, the market driven needs will more clearly identify the suite of coals that will satisfy the markets and the performance requirements (i.e., cost, maintenance, energy efficiency, environmental). For now, it is important to provide sufficient quantities of surrogate fuels to enable development testing to proceed. To serve as surrogate fuels, the fuels should have chemical and physical characteristics (ash, sulfur, volatiles, fusion temperature, heat content, particle size distribution, slurry formulation, etc.) that are consistent with projected performance and environmental standards. In addition, these surrogates are to be produced using readily available conventional types of cleaning and processing so as to not promote a particular fuel technology or create a reliability on an uncertain fuel technology.

Although the future market for deeply-cleaned coal-based fuels is not yet defined, reasonable assumptions can be made regarding the coal types and coal processes that will be needed based on availability of coal resources, projected combustion system performance requirements, and anticipated emissions regulations. The analysis of fuel needs, the selection of candidate coals and the characterization and supply in this contract were accomplished with this in mind. The best coal and fuel choices of those available have been made based upon the available information, coal and processes. This provided the developmental test fuels that enabled the DOE-PETC advanced combustion and fuels program to move forward.

3.0 OBJECTIVES AND SCOPE OF WORK

3.1 Contract Objectives

Contract objectives were as follows:

- Develop fuel specifications to serve combustor requirements.
- Select coals having appropriate compositional and quality characteristics as well as an economically attractive reserve base.
- Provide quality assurance for both the parent coals and the fuel forms.
- Deliver premium coal-based fuels to combustor developers as needed for their contract work.

3.2 Contract Scope of Work

Energy International, with the help of other team members, performed the following:

- From information obtained both from the combustor PRDA and from the combustor contractors, developed fuel specifications and schedule.
- Using published reports and databases, performed a market assessment and a resource assessment in order to identify acceptable coals within reasonable proximity to markets. In other words, determined the availability and applicability of a wide range of coals in order to produce premium coal-based fuels for specific markets.
- From all coal ranks and all domestic resources selected coals which satisfied the requirements of combustion systems were developed.
- Procured premium coals having the ability to be processed to contain <0.8 lb ash per million Btu and <0.5 lbs sulfur per million Btu.
- Procured coals and produced coal liquid mixtures or dry pulverized coal and delivered those premium fuels to combustor contractors.

3.3 Task 1 Objectives

The objectives of Task 1, "Analysis of Fuels Needs", were as follows:

- To provide analyses, information and evaluation of coal resources, coal properties, and market opportunities to support the selection of coals for characterization, processing and supply.

- To assure that coals used in developmental testing are representative of future potential coal used in those applications and are:
 - Available as U.S. domestic resource in sufficient quantity.
 - Geographically proximate to the regional markets.
 - Capable of being processed into premium coal-based fuels that have the properties to satisfy the combustor needs and market constraints (such as environmental).
- To evaluate, interpret and assess the available information on coal reserves, market opportunities, performance requirements, environmental acceptability, coal properties and specific characteristics to provide guidance in the selection of candidate coals for characterization and supply for developmental testing of advanced combustors for residential, commercial and light industrial applications.
- To collect, review and evaluate information about specific, currently available coals that can be procured from existing mining operations to provide contracted quantities of development test fuels that satisfy the reserves, market, geographic, property, performance and environmental criteria.
- To recommend candidate coals and then select specific coals to be purchased, processed into coal-based premium fuels, and supplied to DOE users.
- To coordinate the performance requirements of combustor developers under DOE-PETC contract and in-house efforts with the selection and supply of coals.

3.4 Task 2 Objectives

The objectives of Task 2, "Characterization of Coal Based Fuels", were as follows:

- To procure representative samples of the coals selected in Task 1 and prepare them for characterization studies.
- To obtain baseline analytical data for each of the parent coals.
- To carry out bench-scale froth flotation cleaning tests on each of the candidate coals to determine the yield of specification coal attainable from each.
- To carry out detailed washability studies for each coal to determine the effect of particle size reduction on mineral matter liberation as well as the coal yield as a function of the specific gravity of the separation.

- Using the available results of the characterization studies, to select a coal or suite of coals suitable for the preparation of the fuels to meet the specifications of the combustor contractors.

3.5 Task 3 Objectives

The objectives of Task 3, "Fuel Supply", were as follows:

- To arrange for the capability, availability, and operation of a suitable deep-cleaning coal wash circuit, coal/water slurry preparation plant, and micronizing/grinding facilities.
- To purchase and arrange for the delivery of the appropriate coals for fuel preparation.
- To clean the coals to meet the specifications necessary for the specific fuel needs, i.e., quality categories, such as slagging, non-slagging, industrial retrofit, residential/commercial.
- To prepare the coal based fuels according to the specifications of the PRDA and as modified or requested by the combustor contractors.
- To deliver the fuel to the combustor contractor on schedule.
- To characterize each fuel prior to shipment to assure that the specifications are being met.

4.0 TASK 1 - ANALYSIS OF FUEL NEEDS

4.1 Survey of Combustor Contractors Fuel Needs and Development of Fuel Specifications

In order to establish the types and quantities of fuels necessary to carry out the Department of Energy's Advanced Combustor Program, a fuel specification and supply survey was sent to each of the combustor contractors. The survey forms sent to each contractor are shown in Figures 4.0-1 and 4.0-2. Based on their replies to this survey, along with the specifications detailed in the original PRDA, a set of specifications for each of the fuel types was established. These specifications are given in Tables 4.0-1 and 4.0-2. While there may be some variances for an individual contractor, these specifications are consensus requirements and covered 90% of the fuel requirements for this program.

It can be seen that there are slightly different specifications for the fuel depending upon whether it is a solid or slurry fuel and whether it is for the residential, commercial or light industrial market. Not surprising, however, is the necessity for all fuels to be low in ash (except for the slagging combustors) and low in sulfur to meet current and anticipated emission standards. These emissions requirements (0.8 lbs/mm Btu for ash and 0.5 lbs/mm Btu for sulfur) then dictated that the coal selection process be based upon cleanability criteria as well as the reserve base and the proximity to markets.

The fuel requirements defined by the combustors also indicated the necessity for a high ash fusion temperature (again, except for the slagging combustors) to prevent fouling and slagging in the combustion chamber. This value is generally greater than 2200°F and must be the value for the clean, rather than the parent, coal. This then became another criteria for the coal selection process.

The fuel requirements as determined from the survey and conversations with the combustor contractors indicate that, over the life of the contract, a total of 100 to 200 tons of solid coal and from 75 to 100 thousand gallons of coal-water slurry may be required. The exact amount will depend upon the success the contractors attain as they move through the various development stages.

4.2 Coal Resources and Market Assessment

The approach used for this part of Task 1 focused on the premises reviewed in the Introduction and Background Section, the stated Task Objectives, and, the need to use currently available information, coals and processing in order to supply actual coal fuels meeting representative specifications and in sufficient quantities to satisfy developmental testing needs. Therefore, the approach was to employ the results of previous DOE-sponsored studies, including broad-scale market assessments, national coal data compilations, current mining reserves and records, progress reports on fuels and combustion system requirements. This was supplemented as appropriate by other documents from state-sponsored studies and commercial publications.

Figure 4.0-1

Fuel Specification and Supply Survey

MICRONIZED COAL

1. Coal Rank:	_____		
	Min.	Max.	Preferred
2. % Moisture	_____	_____	_____
3. % Fixed Carbon (MF)*:	_____	_____	_____
4. % Volatiles (MF):	_____	_____	_____
5. % Ash (MF):	_____	_____	_____
6. % Sulfur (MF):	_____	_____	_____
7. Heating Value, Btu/lb. (MF):	_____	_____	_____
8. Ash Fusion Temperature**:	_____	_____	_____
9. Particle Size: Mean:	_____	_____	_____
Top Size:	_____	_____	_____

* MF=moisture free

** Initial softening in reducing atmosphere

Schedule Requirements.

Amount

Date Needed (or Lapsed Time
from Contract Start)

Coals Previously Tested

Submitted By: _____ For: _____
(Name) (Company)

Figure 4.0-2

Fuel Specification and Supply Survey

COAL - WATER SLURRY

For Coal

1. Coal Rank:	_____	_____	_____
	Min.	Max.	Preferred
2. % Moisture	_____	_____	_____
3. % Fixed Carbon (MF)*:	_____	_____	_____
4. % Volatiles (MF):	_____	_____	_____
5. % Ash (MF):	_____	_____	_____
6. % Sulfur (MF):	_____	_____	_____
7. Heating Value, Btu/lb. (MF):	_____	_____	_____
8. Ash Fusion Temperature**:	_____	_____	_____

*MF= moisture free

** Initial softening in reducing atmosphere

For Slurry

1. Solids Loading:	_____	_____	_____
2. Viscosity at Shear Rate:	_____	_____	_____
3. Particle Size: Top Size:	_____	_____	_____
Mean Size:	_____	_____	_____

Schedule Requirements.

Amount

Date Needed (or Lapsed Time
from Contract Start)

Coals Previously Tested

Submitted By: _____ For: _____
(Name) (Company)

Table 4.0-1

Specifications For Solid Coal
DOE Contract No. DE-AC22-86PC90258

Fuel Type	Coal Rank	Particle Size (mean)	Max Topsize µm	% Volatile Matter	% Ash	% Sulfur	BTU Content	Ash Soft. Temp., deg F
Residential	bituminous	10	40	30-55	<1	<1	13,500	>2100
Commercial	bituminous	10	40	30-55	<1	<1	13,500	>2100
Lt. Industrial	bituminous	40	150	30-55	<6	<1	13,500	>2100

Table 4.0-2

Specifications for Coal Water Mixtures
DOE Contract No. DE-AC22-86PC90258

Fuel Type	Coal Rank	% Volatile Matter	% Ash	% Sulfur	BTU Content	Ash Soft. Temp., deg.F	Particle Size (mean)	Max Topsize µm	% Solids	Viscosity cps
Residential	bituminous	30-55	<1	<1	10,000	>2600	10	40	65-70	<1000 2110/sec
Commercial	bituminous	30-55	<1	<1	10,000	>2600	40	150	65-70	<1000 2110/sec
Lt. Indust.	bituminous	30-55	<6	<1	10,000	>2600	40	150	65-70	<1000 2110/sec 70 deg F

Note: Particle size is in microns.

The methodology employed and the results of the assessment are given in the Topical Report "Analysis of Fuel Needs and Selection of Candidate Coals", presented in Appendix A.

4.3 Selection of Candidate Coals

The recommended candidate coals for the stringent fuels requirements for the residential, commercial, and light industrial market segments (RCLI) fuels are presented in Table 4.0-3. From these recommended candidates, it was anticipated that a coal fuel source of representative qualities would be identified and characterized as the baseline RCLI fuel (see Section 5.5). In addition, an option for supplying the Western, Northern Great Plains, and Rocky Mountain regions has been provided by including the Colorado coal, even with lesser reserves identified. Recommendation of additional candidates to supplement the baseline fuel supply can be made, if appropriate, using the information collected in this task.

The most current listing of candidate coals for slagging combustors is presented in Table 4.0-4. A final screening and evaluation is yet needed to present recommended coals for slagging combustors.

Table 4.0-3

CANDIDATE COALS FOR RESIDENTIAL,
COMMERCIAL, AND LIGHT INDUSTRIAL MARKETS

<u>Bed Number</u>	<u>Coal Bed Name</u>	<u>Related Names</u>	<u>Locations Found</u>	<u>Original Estimated Reserves (tons)</u>
151	Upper Elkhorn #3	Cedar Grove, Jellico, Taggart	WV,VA,KY,TN	12,558,191,000
154	Upper Elkhorn #2	Lower Cedar Grove	WV,VA,KY	3,525,101,400
157	Upper Elkhorn #1	Alma, Blue Gem	WV,VA,KY,TN	9,402,073,300
168	Lower Elkhorn	No. 2 Gas, Pond Creek	WV,VA,KY,TN	11,015,747,000
755	Coal Basin D	Oliver	CO	83,000,000

Table 4.0-4

CANDIDATE COALS FOR SLAGGING COMBUSTORS

<u>Rank</u>	<u>Bed No.</u>	<u>Coal Bed Name</u>	<u>Related Names</u>	<u>Locations Found</u>	<u>Original Estimated Reserves (10⁶ tons)</u>
B	63	Lower Bakerstown	Thomas Three Foot	MD,PA,WV	540
B	71	Upper Freeport	Big Vein	MD,OH,WV, PA,KY	8,556
B	77	Princess No. 7	Coalton	KY	138
B	151	Upper Elkhorn #3	(See Table 4.0-3)	WV,VA,KY,TN	12,558
S	154	H-Seam		CO	253
S	169	Upper Williams		CO	183
B	214	Upper Banner		KY,VA	256
B	269	Tiller	Lower Iaeger	WV,VA	166
B	495/ 496	Deadman (Upper/Lower)			190
S	496	Croweburg	Fireclay No. 2	KN,OK,MO	579
S	697	Dietz #3	Canyon	WY,MT	2,538
S	699	Anderson- Wyodak		MT,WY	18,373
S	768	Laramie No. 3		CO	302
S	672	Adaville		WY	932
S	927	Anderson/Dietz		MT,WY	3,858

Rank: S = subbituminous
B = bituminous

5.0 TASK 2 - CHARACTERIZATION AND FORMULATION OF COAL BASED FUELS

5.1 Procurement and Sampling of Candidate Coals

Two fifty-five gallon drums of coal were obtained from each of the five coal beds selected and approved on January 26, 1987. The parent coals are identified in Table 5.0-1 along with the source and location of each coal.

Each coal sample from each coal bed was obtained from operating facilities that utilize conventional cleaning equipment. Each sample was taken from stockpiles at its respective plant with no special plant operation being utilized. Proper sampling methods were utilized to the extent possible to insure representative samples of each coal seam. After obtaining the samples, the drums were shipped to Dravo for sample preparation and characterization.

5.2 Analysis of Candidate Coals

Upon receipt of the parent coal samples, the two drums were blended and then split into two portions. One portion was placed back into one drum, sealed, and stored for future use if needed. Coal in the second drum was screened and crushed to minus 1/8 inch using an impact mill. The minus 1/8 inch material was then reblended and samples taken for characterization studies.

A sample of each parent coal was submitted for proximate, ultimate, ash chemistry, ash fusion, and Hardgrove grindability. The test results are given in Table 5.0-2

5.3 Washabilities of the Candidate Coals

The most important part of Task 2 of the fuel supply contract was to carry out washability studies on coals selected in Task 1. This was to determine which of the selected coals could be cleaned to produce compliance fuels (low ash, low sulfur) for the DOE combustor program. It was necessary, therefore, to carry out washability studies of the coals ground to different particle sizes to determine the effect of grinding upon mineral matter liberation. That is, could a particular coal yield a low ash, low sulfur product if ground to a small enough particle size before cleaning? It was decided to determine the washability of each coal at particle sizes of -1/8 inch, -28 mesh, -100 mesh, and -200 mesh. In addition, each of these fractions would be sieved to obtain fractions of 1/8" x 28 mesh, 28 x 100 mesh, 100 x 200 mesh, 200 x 270 mesh, 270 x 400 mesh and -400 mesh to determine in what, if any, particle size fraction the mineral matter would be concentrated. Therefore, the matrix of samples prepared is shown on page 19.

Table 5.0-1

SELECTED COALS FOR RESIDENTIAL, COMMERCIAL
AND LIGHT INDUSTRIAL MARKET

<u>Bed Number</u>	<u>Coal Bed Name</u>	<u>Related Name</u>	<u>Coal Source</u>	<u>Mine/ Plant</u>	<u>Mine Location</u>
151	Upper Elkhorn #3	Cedar Grove Jellico	Westmoreland Coal Compoany	Wentz Plant	Big Stone Gap, VA
154	Upper Elkhorn #2	Lower Cedar Grove	Beth Energy	Damron Plant 29	Jenkins, KY
157	Upper Elkhorn #1	Alma, Blue Gem	Old Ben Coal Company	Mine #20	WV
168	Lower Elkhorn	No. 2 Gas, Pond Creek	Mapco	Pontiki	Lovely, KY
755	Coal Basin D	Oliver	Westmoreland Coal Company	Orchard	Paonia, CO

Table 5.0-2

PARENT COAL ANALYSIS

Dry Basis

<u>Analysis</u>	<u>Upper Elkhorn #3</u>	<u>Upper Elkhorn #2</u>	<u>Upper Elkhorn #1</u>	<u>Lower Elkhorn</u>	<u>Coal Basin D</u>
Bed No.	151	154	157	168	756
Seam Name	Taggart	Lower Cedar Grove	Alma	Pond Creek	Colorado
Coal Co.	Westmoreland Coal Co.	Central Coal Co.	Old Ben	Westmoreland Coal Co.	Westmoreland Coal Co.
Proximate:					
Volatile Matter	35.97	35.50	34.13	35.12	39.60
Fixed Carbon	61.78	58.98	59.69	57.98	53.80
Ash	2.25	5.52	6.18	6.90	6.60
Sulfur	0.62	0.52	0.83	0.57	0.53
Btu/lb	14829	14331	14381	13763	12945
Ultimate:					
Carbon	83.23	80.57	80.79	75.46	72.80
Hydrogen	5.14	4.81	4.76	4.81	4.78
Nitrogen	1.51	1.49	1.46	1.63	1.68
Ash Chemistry:					
SiO ₂	45.27	54.61	48.96	51.03	61.95
Al ₂ O ₃	30.17	29.71	27.82	30.81	21.21
TiO ₂	1.40	1.61	1.50	2.18	0.82
Fe ₂ O ₃	13.26	7.49	12.24	6.32	5.47
CaO	2.56	1.61	2.38	2.92	2.39
MgO	1.06	0.91	1.13	0.88	1.06
K ₂ O	1.82	2.37	2.35	2.22	1.34
Na ₂ O	1.57	0.29	0.74	0.69	3.12
SO ₃	1.75	0.88	2.40	2.54	1.29
P ₂ O ₅	0.14	0.18	0.12	0.07	0.69
SrO	0.33	0.25	0.22	0.19	0.22
BaO	0.24	0.18	0.14	0.15	0.29
Mn ₃ O ₄	0.00	0.00	0.00	0.00	0.00
Base Acid Ratio	0.26	0.15	0.24	0.16	0.16
T 250 Temperature	2599	2872	2640	2832	>2900
Ash Fusion					
Reducing Atmos.					
Initial	2560	2560	2350	2560	2200
Softening	2692	2690	2470	2670	2310
Fluid	+2700	2780	2600	2760	2440
Hardgrove	58	44	53	44	51

Note: See Coal Analysis Notes at the beginning of Appendix K.

MATRIX OF SAMPLES PREPARED

	<u>1/8"x28</u>	<u>28x100</u>	<u>100x200</u>	<u>200x270</u>	<u>270x400</u>	<u>-400</u>
-1/8"	X	X	X	X	X	X
-28 mesh		X	X	X	X	X
-100 mesh			X	X	X	X
-200 mesh				X	X	X

Each sample (except the -400 mesh sample) was then sink/floated at specific gravities of 1.25, 1.275, and 1.3. Higher gravities were not used because we were looking for products with ash contents of 1.3% or less.

The sink/float testing of the larger particle size ranges (>100 mesh) can be carried out in laboratory glassware designed for this purpose. This technique depends upon gravitational forces to effect the separation. However, at particle sizes less than about 100 mesh, gravitational forces either take an inordinately long time or are ineffective in bringing about separations. To obtain separations of these small particles it is often necessary to subject the sample to centrifugal forces. Therefore, washability studies of the 100x200, 200x270 and the 270x400 fractions were done with the aid of the centrifuge. As the work progressed it was noticed that very little float product was obtained for these fractions for the -1/8" and -28 mesh products. At that time it was felt that this was because the clays and other mineral matter were concentrated in the smaller particle size fractions which would result in less float product. However, when the 200x270 mesh fraction of the -200 mesh product for the Upper Elkhorn #3 coal gave almost 100% sink at 1.25 specific gravity it was realized that our technique was faulty and our results erroneous. At the present time there is no standard method for carrying out centrifugal washabilities nor even an industry wide consensus as to the best method. The same difficulties we encountered have been experienced by many investigators.

The initial washabilities of the candidate coals are given in Tables 5.0-3 through 5.0-6. It can be seen that at the smaller particle size ranges, done by centrifuge, there is little or no float product for any of the coals.

After a brief review of the literature and other publications, it was decided to try a centrifugal method suggested by AMAX Coal Company. In this method the fine coal is first placed into the centrifuge tubes and then the heavy liquid medium (Certigrav) of the selected specific gravity containing 500 ppm of the dispersant Aerosol OT is added. The coal is then dispersed by stirring with a brass rod followed by a 2 minute treatment in an ultrasonic bath before centrifugation. This method was used to repeat the washability studies on the 100x200, the 200x270, and the 270x400 fractions from each of the four grind sizes for the Upper Elkhorn #3 coal. The results of the washability tests are summarized in Table 5.0-7 and the washability curves for each of the four grind sizes are shown in Figures 5.0-1, 5.0-2, 5.0-3, and 5.0-4. This technique gave much more consistent

file:sfuola
update:08/03/87

Analyses of Screened Fractions

Float /Sink Analysis

Float /Sink Analysis

Float /Sink Analysis

Float /Sink Analysis

Floot /Sink Analysis

[illegible]

file:sfue2a
update:08/03/87

Screen analysis

Analyses of Screened Fractions

Fraction	Weight	Zwt.	Each Fraction (Dry Basis)		BTU	Cumulative			
			%Ash	%Sul		Zwt.	%Ash	%Sul	BTU
1/8m28	937.00	70.20	5.26	0.56	14003	70.20	5.26	0.56	14003
28m100	234.23	17.55	5.34	0.67	13726	87.75	5.27	0.56	13948
100m200	69.58	4.46	5.25	0.69	13909	92.22	5.27	0.57	13946
200m270	20.99	1.57	5.50	0.60	13680	93.79	5.28	0.57	13942
270m400	14.15	1.06	5.55	0.56	13954	94.85	5.28	0.57	13942
400m	66.72	5.15	10.41	0.52	12957	100.00	5.54	0.56	13891
TOTAL	1334.67	100.00							

Size: 1/8" #20 mesh fraction

Float /Sink Analysis

[illegible]

Size: 20-100 mesh fraction

Float /Sink Analysis

[illegible]

Size: 100x200 mesh fraction

Float /Sink Analysis

[illegible]

Size: 200µ270 mesh fraction

Float /Sink Analysis

[illegible]

Size: 270x400 mesh fraction

Float /Sink Analysis

[illegible]

file:sfue3a
update:08/03/87

Analyses of Screened Fractions

[illegible]

file:zflela
update: 11/4/87

Fraction	Height	Wt.	Each Fraction (Dry Basis)		BTU	Cumulative			
			Wt.	Wul		Wt.	Wul	BTU	
1/8m28	818.20	67.04	6.16	0.55	13200	67.84	6.15	0.55	13200
2m100	222.64	18.46	5.97	0.59	13157	86.30	6.11	0.56	13191
100m200	59.56	4.94	5.61	0.65	13141	91.24	6.09	0.56	13188
200m270	19.45	1.61	6.36	0.77	13298	92.85	6.09	0.57	13190
270m400	20.08	1.66	6.19	0.73	13289	94.51	6.09	0.57	13192
400m0	66.16	5.49	11.78	0.61	12176	100.00	6.41	0.57	13136
TOTAL	1206.09	100.00							

[illegible][illegible][illegible][illegible][illegible]

Table 5.0-7

COAL-WATER FUEL SPECIFICATIONS

<u>Type</u>	<u>% Solids</u>	<u>Particle Top Size, μm</u>	<u>Mean Particle Diameter, μm</u>	<u>@ 100/sec. cps</u>
Standard Grind (2.5-3.0% Ash)	60-70	149	20-40	<1000
Standard Grind (1.3-1.5% Ash)	60-70	149	20-40	<1000
Micronized (2.5-3.0% Ash)	60-70	44	10-20	<1000
Micronized (1.3-1.5% Ash)	60-70	44	10-20	<1000

Figure 5.0-1

WASHABILITY CURVES FOR UPPER ELKHORN #3 COAL

Figure 5.0-2

WASHABILITY CURVES FOR UPPER ELKHORN #3 COAL

Figure 5.0-3

WASHABILITY CURVES FOR UPPER ELKHORN #3 COAL

Figure 5.0-4

WASHABILITY CURVES FOR UPPER ELKHORN #3 COAL

and logical results. Surprisingly, when comparing the yield and ash content of the 1.3 float fraction there is little or no improvement in ash liberation by grinding smaller than 1/8 inch topsize. The results indicate that ideally a 90% yield of a 1.0% ash product should be attainable.

5.4 Bench-scale Flotation Testing

5.4.1 Procedure

Bench-scale flotation tests were performed on all coal samples except the Coal Basin D Seam. Testing was performed using either a Denver or Wemco flotation cell. Samples were ground for the specified period of time using either rods or balls in a laboratory Abbe mill with the ground coal then placed into the flotation cell. A frother was then added and conditioned for at least 30 seconds. Air was then turned on and the froth removed for three minutes or until no additional froth could be obtained. The flotation procedure followed the Penn State starvation flotation method followed by at least two stages of cleaning of the froth product. Samples of all tailing products and the final froth were submitted for ash analysis. Test results for each seam follow.

5.4.2 Upper Elkhorn #1

Twelve flotation tests were performed on the Upper Elkhorn #1 (UE1) seam. Both grinding time and frother addition were varied to try to obtain maximum recovery of less than 1.5% ash in the final froth. As shown in Figure 5.0-5, the UE1 coal could produce ash in the range, however, recoveries were less than 15%. When trying to obtain one percent ash in the final product, recoveries approached 5% or less. Figure 5.0-5 also indicates that additional grinding beyond 30 minutes was not beneficial and the ultimate grind appears to be between 10 and 30 minutes. Higher frother addition rates increased recovery but reduced quality.

5.4.3 Upper Elkhorn #3

Five flotation tests were performed on the Upper Elkhorn #3 (UE3) seam. As shown in Figure 5.0-6 both grinding time and frother addition were varied in an attempt to obtain a final ash product of less than 1.5% and 1.0%. The UE3 coal produced significant quantities of both qualities with minimal report, with over 60% recoveries of 1% ash in the final flotation product. These high recoveries appear to be influenced by the low ash content of 2.5% in the UE3 feed, which is approximately 50% less in ash than the other seam samples. However, the UE3 coal floats very easily and should be a prime candidate for use in the production of the bulk samples for pilot plant operation.

5.4.4 Upper Elkhorn #2

Figure 5.0-7 shows the results of some of the flotation studies on the Upper Elkhorn #2 coal. In this particular study the starvation flotation procedure was not used, i.e., in some cases additional frother was added between stages in an effort to increase the yield. Longer grind times were used to determine if better ash liberation could be achieved by reducing the particle size and the effect of the use of dispersants was also evaluated. It can be seen that a 1.5% ash product can be obtained with

Figure 5.0-5
Upper Elkhorn #1
Froth Flotation Cleaning
(Three Stage)

Figure 5.0-6
Upper Elkhorn #3
Froth Flotation Cleaning
(Three Stage)

Figure 5.0-7
Upper Elkhorn #2
Froth Flotation Cleaning
(Three Stage)

greater than a 50% yield. This was very encouraging since the parent coal had an ash content of greater than 5%. It is felt that with further refinement a reasonable yield of 1% or less ash content is achievable. This makes the Upper Elkhorn #2 coal an excellent candidate for the production of ultra-clean coal for the preparation of premium fuels for the combustor program.

5.4.5 Lower Elkhorn

As with the Upper Elkhorn #2 coal, flotation studies were carried out with the Lower Elkhorn coal using longer grind times, higher frother concentrates and with and without the use of chemical ash dispersants. The results are shown in Figure 5.0-8. A 40% to 50% yield of a 2.5% ash product was achieved. In this case it can be seen that increasing the grinding time from 60 to 120 minutes did not improve ash rejection and it drastically reduced the clean coal yield. The use of dispersants not only did not improve the yield but generally produced a higher ash product. These results indicate that, for this coal, obtaining a 1% or less ash product at a reasonable yield will be more difficult. The results of the washability studies described in the previous section will give a better indication of the ultimate cleanability of each of the candidate coals and help determine the best method for cleaning the coals.

5.5 Selection of Baseline Coal

As indicated by the flotation test work, the Upper Elkhorn #3 seam yielded the highest recoveries at the lowest ash percent of the four seams treated thus far. The UE3 capability for such high recoveries, while capable of producing a wider range of low ash values, makes the UE3 seam very flexible in supplying initial requirements for many of the DOE combustor contractors, and was therefore chosen to become the designated parent or base coal for the fuel supply program.

5.6 Coal-Water Fuel Development

5.6.1 Selection of a Coal-Water Fuel Manufacturer

A fully documented procurement procedure was implemented in order to identify and select a coal-water manufacturer.

A survey of the primary slurry manufacturers was carried out to determine their current status, capabilities and willingness to participate in the advanced combustor program for the contract term.

(remainder of page intentionally left blank)

Figure 5.0-8
Lower Elkhorn Coal
Froth Flotation Cleaning
(Three Stage)

Based upon the replies to the survey and follow-up discussions with the vendors, OXCE Fuel Company was chosen to provide slurry fuels for this program. They were fully qualified to meet the requirements of the program and indicated a willingness to participate during the full term of the contract.

Near the end of the contract some slurry was purchased from AMAX Coal Company through their Research & Development Center in Golden, Colorado. This effort is discussed in Section 5.6.2.

After selection of the Upper Elkhorn #2 coal as the baseline coal, a purchase order was issued to OXCE Fuel Company to do the necessary formulation work to prepare specification slurries from a washed run-of-mine (2.5-3.0% ash) and from a deep cleaned (1.3-1.5% ash) wet filter cake prepared by Dravo (see Section 6.2). The results of their formulation efforts are described in Appendices B and C. They were successful in preparing good stable slurries having the specified top sizes, viscosities and mean particle diameters, etc. Table 5.0-7 gives the specifications for the two types of slurries developed and used by most of the combustor contractors.

5.6.2 Slurry Fuel Preparation by AMAX Coal Company

In an attempt to respond to an urgent delivery request by MTCI for 800 gallons of a coal-water slurry fuel, Energy International contacted AMAX Research and Development Center in Golden, Colorado to see if they could prepare the needed slurry. They said they could start almost immediately. Therefore 8,800 lbs. (in 28 drums) of an Upper Elkhorn #3 coal containing 4.6% ash was shipped on February 7 to AMAX for the slurry preparation.

Their first attempt resulted in a slurry with much too low solids content (58.61% solids). This was due to a water leak into the slurry mixing tank due to defective equipment. During Energy International's routine quality control evaluation of the slurry, it was found that not only was the solids content below specification (>62%) but also that the average particle size as measured by the Micro-Trac system was 10.08 microns -- much smaller than the specified 30 microns. In fact, the particle size distribution was more like a micronized coal-water slurry than a utility grind slurry.

Upon realizing the low solids content of the slurry, AMAX evaporated some of the water to produce a slurry containing 62.64% solids. A sample of this product was sent to Energy International for evaluation. We confirmed that the solids content had been increased and we observed the same particle size distribution as that in the first sample; but now the measured viscosity was much higher than requested. We measured a viscosity of 1133 cps at 100/sec by our standard procedure using the Haake rotational viscometer. The specifications called for a viscosity of no greater than 500 cps at a shear rate of 100/sec. The data obtained for the slurries is compared to the requested specifications in Table 5.0-8.

Table 5.0-8

PROPERTIES OF COAL-WATER SLURRIES
PREPARED BY AMAX RESEARCH & DEVELOPMENT CENTER

<u>Property</u>	<u>UE3-217(a)-CWF-G</u>	<u>UE3-217-(b)-CWF-G</u>	<u>Spec.'s</u>
Solids, Wt. %	58.6	62.6	>62
Viscosity, cps at 100/sec.	391	1133	<500
Mean Diameter (volume), microns	10.8	9.98	30

AMAX claimed a viscosity of 432 cps at 100/sec for the second slurry, UE3-217-(b)-CWF-G, and therefore, with the exception of the mean diameter (volume) (MW on Microtrac), considered it to be within specifications. In a further conversation with them it was determined that they had been using a capillary viscometer to measure their viscosities. In order to check their value we measured the viscosity of slurry UE3-217(b) using the Burrell Extrusion Tube Rheometer. The data obtained are shown in Table 5.0-9 and graphically in Figure 5.0-9. It can be seen that at about 107/seconds the viscosity that was obtained was 411 centipoise, very close to their value of 432 cps at 100/sec. Therefore, it will be important in the future not only to specify the desired viscosity but also the method of measurement.

A comparison of the particle size distributions of the AMAX slurry, UE3-217(b), and a typical utility grind slurry from another slurry maker is shown in Figures 5.0-10 and 5.0-11. It can be seen that there is a large concentration of very small particle sizes in the AMAX slurry. In fact, the AMAX slurry could be considered a micronized slurry with a mean mass diameter of 10 microns and with only a very small percentage of particles larger than 44 microns.

In an effort to alter the particle size distribution and to more closely approximate a standard "utility grind" slurry, AMAX attempted to reformulate the slurry by blending in an amount of a coarser ground coal. This resulted in a slurry with properties shown in Table 5.0-10.

It can be seen that the properties of the reformulated slurry are closer to those specified. A comparison of the particle size distribution of the reformulated slurry, UE3-217(c) with the first slurry, UE3-217(b), can be seen by comparing Figure 5.0-11 and Figure 5.0-12. It can be seen that there is some broadening of the distribution due to blending in of a coarser ground coal.

Because of the inability to initially meet our specifications in their first attempt, AMAX offered to prepare, at their own expense, an additional 800 gallons of a utility grind slurry for use by MTCI. Accordingly, Energy International shipped 5,300 lbs of the Upper Elkhorn #3 coal (UE3-201-WRM-E) to Amax. From this coal a slurry was prepared which met specifications. Thirteen barrels of the slurry (UE3-222-CWF-G) was, with prior approval, then shipped to MTCI.

5.6.3 Slurry Characterization

The following is a list of methods which were routinely used for the characterization of coal-water fuels. Not only were they used to assure that there is little or no variation between batches of the same slurry (quality control) but also to help in the understanding of the effect that variations of these parameters will have on handling, pumping, combustion, carbon burn out, etc., when comparing different slurries.

Table 5.0-9

High Shear Viscosities of Amax Slurry (UE3-217(b)-CWF-G)

BURELL EXTRUSION TUBE RHEOMETER										
Run No.	Orifice R, cm.	Pressure psi	Pressure dynes/cm	Time sec	Weight gms	Volume ml	Q ml/sec	Shear Rate (1)	Shear Stress (2)	Viscosity cps (3)
1	0.15	5.00	3.45E+05	10.36	22.84	19.34	1.87	704	2.59E+05	735
2	0.15	5.00	3.45E+05	10.00	26.34	22.30	2.23	842	2.59E+05	615
3	0.15	5.00	3.45E+05	10.00	25.44	21.54	2.15	813	2.59E+05	637
							Average =	786		662
4	0.15	10.00	6.90E+05	10.08	41.31	34.98	3.47	1309	5.18E+05	790
5	0.15	10.00	6.90E+05	9.81	38.16	32.31	3.29	1243	5.18E+05	833
6	0.15	10.00	6.90E+05	9.90	37.12	31.43	3.17	1198	5.18E+05	864
7	0.15	10.00	6.90E+05	10.08	43.37	36.72	3.64	1375	5.18E+05	753
							Average =	1281		810
8	0.15	15.00	1.04E+06	10.20	55.76	47.21	4.63	1747	7.76E+05	889
9	0.15	15.00	1.04E+06	10.01	54.27	45.95	4.59	1732	7.76E+05	896
							Average =	1739		893
10	0.15	0.4408	3.04E+04	31.54	10.61	8.98	0.28	107	2.28E+04	424
11	0.15	0.4263	2.94E+04	30.24	10.25	8.68	0.29	108	2.21E+04	407
12	0.15	0.4104	2.85E+04	30.22	10.03	8.49	0.28	106	2.12E+04	401
							Average =	107		411

(1) Shear Rate (1/sec.) = $4Q/\pi R^3$

(2) Shear Stress (dynes/cm.) = $\pi R^2 L$

(3) Viscosity (poise) = $\pi R^4 / 8 L Q$

where: P = pressure in dynes/square centimeter

R = Radius of orifice in cm.

L = Length of orifice in cm.

Q = quantity extruded in milliliters per second
(vol. in ml. = weight in grams/sp. gr.)

Figure 5.0-9
Burrel Extrusion Tube Rheometer
Viscosity vs Shear Rate

FIGURE 5.0-10
Particle Size Distribution
Amax Slurry UE3-217(b)-CWF-G

FIGURE 5.0-11
Particle Size Distribution
Slurry UE3-188-CWF-F

Table 5.0-10

PROPERTIES OF REFORMULATED SLURRY

<u>Property</u>	<u>UE3-217(c)-GFF-G</u>	<u>Spec.'s</u>
Solids, Wt. %	62.4	>62
Viscosity, cps at 100/sec.	633	<500
Mean Diameter (volume), microns	14.8	~ 30

5.6.3.1 Percent Solids

The solids content of the coal-water slurry is determined by evaporating to dryness a two to three gram sample of the slurry in a tared porcelain crucible at 110°C under a nitrogen purge at a reduced pressure of about 15 inches of Hg. After cooling and reweighing, the solids content of the slurry is calculated as:

$$\% \text{ Solids} = \frac{\text{Weight Sample after Drying}}{\text{Weight Sample before Drying}} \times 100$$

5.6.3.2 Percent Ash

The sample used for the % solids determination (described above), still in the tared crucible, is then heated in the Fisher programmable ashing furnace by heating from room temperature to 500°C at a heating rate of 8°C/min., holding at 500°C for 15 minutes and then heating to 750°C at a 5°C/min. heating rate. The sample is held at 750°C for one hour and then the oven is turned off. After the oven has cooled to near room temperature the crucible is removed and allowed to cool to room temperature in a desiccator. The cooled crucible is then weighed rapidly and the percent ash calculated as follows:

$$\% \text{ Ash} = \frac{\text{Weight Sample after Ignition}}{\text{Weight Sample before Ignition}} \times 100$$

5.6.3.3 Hydrogen Ion Concentration (pH)

The pH is measured using a conventional calibrated laboratory pH meter. The objective of a pH specification is to insure that the materials of construction used in the furnace and spraying system will not be corroded or damaged due to the alkalinity or acidity of the coal-water fuel. It is also used as a quality control parameter.

5.6.3.4 Specific Gravity @ Room Temperature

The specific gravity of the slurry is determined at room temperature using a Fisher grease pycnometer. The pycnometer is cleaned and tared. The pycnometer is then filled with water and weighed. After emptying and drying, the pycnometer is then filled with the coal-water slurry and again weighed. The ambient temperature is then recorded. The specific gravity of the slurry is then calculated as follows:

$$\text{Specific Gravity @ RT} = \frac{(\text{Wt. Slurry \& Pyc.} - \text{Wt. Pyc.})}{(\text{Wt. Water \& Pyc.} - \text{Wt. Pyc.})}$$

If the density of the water is assumed to be 1.000 at the measured temperature then the density and specific gravity are interchangeable. If the density of water at the measured temperature is known then the volume of the pycnometer can be determined and the true density of the coal-water slurry (in gms/cc.) calculated.

5.6.3.5 Btu Content

The Btu content of the slurry is estimated from the measured solids content of the slurry and the known Btu content of the coal used to prepare the slurry. The calculation is:

$$\text{Slurry Btu/Lb} = (\text{Wt.\% Dry Coal in Slurry}/100) \times (\text{Btu Content of Dry Coal})$$

5.6.3.6 Viscosity

All viscosity measurements of coal-water slurries are made with the Haake Rotovisco Model RV 100. Viscosities are recorded continuously at shearing rates from 0 to 229 sec^{-1} both in the upward (increasing shear rate) and downward (decreasing shear rate) direction in order to determine if any hysteresis will occur. The measurement is made three times. The viscosity values at 100 and 200 sec^{-1} are interpolated from the computer printout from the third descending curve. The computer also generates the so-called "power law factor" which is the exponential factor, b, from the Ostwald equation:

$$\tau = A \times D^b$$

where τ = the shear stress
D = the shear rate, and
A = correlation coefficient
b = "power law factor"

A value of 1.00 for exponent "b" will turn this equation to the Newton's law of viscosity equation. Values of "b" bigger than 1.00 describe dilatant flow behavior, i.e., increasing viscosity with increasing shear rate, while values less than 1.00 means pseudoplastic flow behavior, i.e., decreasing viscosity with increasing shear rate. Therefore, the degree of non Newtonian behavior of a particular fluid is determined by the deviation of b from 1.00

5.6.3.7 Particle Size Distribution

The particle size distribution of the coal-water slurry is generally reported as the percent of the coal in the slurry that exceeds both 100 and 200 mesh. In addition, the -100 mesh fraction's particle size distribution is determined using the L&N Model Microtrac system. From the Microtrac record the diameter (in microns) of the particle having the mean particle volume is reported. This value along with the value of the slurry's top size (i.e., largest particle size) helps classify the slurry as a utility grind slurry or a micronized slurry. Generally a slurry with 150 micron top size with a mean volume diameter of 20-30 microns is considered a utility grind while a 44 micron top size with a mean particle diameter of 10-15 microns is considered micronized.

5.7 Dry Ground Coal Preparation

As a result of the survey of the combustor contractors, it became apparent that four different dry coal forms would be required over the course of the contract. These forms, along with some minimum specifications, are shown in Table 5.0-11. Since each product required different

Table 5.0-11

DRY GROUND COAL SPECIFICATIONS

<u>Fuel Type</u>	<u>Particle Top Size, um</u>	<u>Mean Particle Diameter, um</u>
Standard Grind (2.5-3.0% Ash)	149	20-40
Standard Grind (1.3-1.5% Ash)	149	20-40
Micronized (2.5-3.0% Ash)	44	10-20
Micronized (1.3-1.5% Ash)	44	10-20

grinding circuitry much effort was utilized in trying to find a company that has the facilities to perform all or most of the required grinding. The following problems evolved during this search:

- Most companies do not have the proper facilities or are reluctant to handle high volatile (>35%) coals.
- Some companies can pulverize to minus 150 microns, but do not have the capabilities to micronize (<44 microns).
- Few companies have drying capability.
- Some companies preferred to grind "white power" and did not wish to contaminate their circuits with coal.
- Some companies have grinding capabilities but are not production oriented. Their facilities are for research and testing to support their sales of equipment.
- Their capacities are too small or they have no available openings in their schedules.

In addition, DOE combustor contractor schedules indicated that a supply of micronized coal was required by April 1, 1987, thereby causing problems in locating an available cost effective producer.

After having discussions with over a dozen potential dry grinding companies, Fluid Energy Company near Philadelphia, PA was selected to initially supply micronizing services for the April requirements. Three days before they were to start, they had an explosion and fire which put them out of operation. This caused an additional backlog at other grinding companies and, therefore, it took until the end of April before obtaining an alternate micronizer, Particle Reduction Services Corporation (PRS) of Oak Grove Village, Illinois.

The grinding equipment used by PRS was an air swept high energy type mill utilizing particle on particle bombardment at a feed rate of about 100 lbs/hr. Assurances were made that specifications were obtained by conducting short test runs to adjust the equipment and then sampling periodically during the run for Microtrac analysis by Dravo or Energy International.

In addition to PRS, Penn Rillton Company, a division of Whibco of West Elizabeth, PA was used during the early stages of fuel production. Even though the deep cleaned coal produced from the Dravo pilot froth flotation unit was 100% less than 150 microns (see Section 6.2) it was necessary to batch dry the coal to less than 5% moisture to produce the "standard" or utility grind fuel. This drying would produce dried clumps of compacted coal. Therefore, the dried clumps of coal had to be broken up to discrete particles again before shipment to the combustor contractors. Penn Rillton was chosen to do this because of its close proximity and having equipment

TABLE 5.0-12

Results of Clean Coal Solicitation
(Procurement Package MN-01-2003)

<u>Firm Contacted</u>	<u>Response</u>	<u>Process Description</u>	<u>Selected</u>
1. Amax R & D Center	no		
2. Ames Laboratory	yes	Multi-stage Froth Flotation	no
3. Alberta Research	no		
4. ARCTECH	no		
5. Atlantic Research	no		
6. Battelle Institute	no		
7. CLITECH A	yes	Chemical Cleaning	no
CLITECH B		Dense Media Sep.	no
CLITECH C		Flotation	no
8. Coaliquid	no		
9. Coal Technology	no		
10. UNDEERC	yes	Heavy Media Cyclone	yes
UNDEERC		Acid Washing	yes
11. CQCD (EPRI)	yes	Heavy Media Sep.	no
CQCD (EPRI)		Froth Flotation	yes
12. EPRI (Alabama)	no		
13. Michigan Tech/IMP	no		
14. Jim Walters Res.	no		
15. OTISCA	yes	T-Process	yes
16. Process Technology	no		
17. Resource Eng.	no		
18. Virginia Tech	yes	Microbubble Column Flotation	yes
19. Westmoreland Coal Co.	yes	Heavy Media Separation	yes

capable of handling bulk tonnages. Feeding the coal into a hammermill equipped with a 28 mesh screen deck guaranteed the desired particle separation. Penn Rillton also had the capability of hydraulically conveying the ground coal particles with a forced air system thus enabling even further drying of the fuel.

The limited production rates of PRS reaffirmed the necessity to seek another grinding service. By the end of June, 1987, a commitment was made by Schutz-O'Neill Company (now Jacobsen, Inc.) of Roseville, Minnesota to supply micronized and pulverized fuels to the combustor contractors. Documents for procurement approval were prepared and subsequently a sub-contractor agreement was signed by the end of July, 1987.

5.8 Availability of Coal Deep Cleaning Services (Procurement Package MN-01-2003)

A request-for-bid package (e.g. MN-01-2003) for the procurement of coal deep-cleaning services was issued to nineteen potential vendors in August, 1989. The intent of the procurements was to: 1) confirm and characterize the capabilities for obtaining premium coal for PETC and their combustor contractors; 2) identify some technology and process candidates for providing the premium-quality test fuels for new commercial ventures; and 3) enable suppliers to obtain the experience base with this coal to provide reasonable scale-up and costing. It was not the intent of this procurement action to evaluate or rank the cleaning capabilities offered on the basis of either technical performance or cost. Each cleaning service obtained was expected to demonstrate an ability to provide the needed clean coal in its own way.

As a supplier of premium-quality fuel to many DOE combustion contractors, Energy International had a need to evaluate and assess capabilities to readily obtain premium-quality test fuels using conventional processing. We were seeking a demonstration of the capability to produce tonnage quantities of a low ash product as a precursor to future fuel requirements. Target properties were 1.2 and 1.5% ash (preferred) or a relaxed 2% ash. In addition, we wanted a demonstration at an appropriate scale of production, i.e., the use of equipment and methods typical of future production needs of the order of 10 to 30 tons; that is, the use of pilot scale (or larger) equipment not bench or lab size.

In response to EI's request-for-bid, fourteen bid proposals from ten organizations were received. "No-Bid" responses were received from three and six did not respond. Ten proposals were judged as suitable to meet the contract objective of demonstrating existing advanced coal-cleaning capabilities. Four bids were rejected for being outside the competitive range based on both price and technical criteria. Having a limited budget, we selected for award as many acceptable proposals as possible. Summaries of bids were reviewed with PETC technical staff and recommendations were made at a September 13, 1989 meeting. Having PETC's concurrence, we issued a Notice of Award/Rejection to all bidders. Purchase orders for five coal cleaning demonstrations were issued with the purpose being to demonstrate a variety of cleaning methods.

Those organizations selected are listed below along with their technology. This set provided a balanced assessment of capabilities.

- Virginia Tech - microbubble column flotation
- Westmoreland Coal Company - heavy media circuit with lower separation specific gravity
- Otisca Industries, Ltd. - Otisca T-process
- Energy & Environmental Research Center - University of North Dakota - dense media separation and continuous acid leaching
- Coal Quality Development Center - froth flotation

Five technologies were selected in order to demonstrate different methods for achieving a premium quality coal product. The selections were made after considering the price of the bid, the suitability of the company's capability for satisfying future premium coal fuel needs, and a balance of deep-cleaning and product form types. The ten well qualified proposals were all judged to be very good, and all ten would have been funded had sufficient funds been available. In order to narrow the selections to the best set of projects for the available funds, the bids were categorized by depth-of-cleaning potential as follows:

- Conventional grinding and heavy media processing with likely potential to reduce ash to the 1.5 to 2.0 percent level.
- Froth flotation with grinding at the 100 mesh top size to achieve the 1.2 to 1.5 percent ash level with improved yield and production cost.
- Advanced processes offering potential to reduce ash levels below 1.2 percent with good yield and cost.

After categorizing the capabilities offered, several combinations of projects were presented as packages and reviewed for demonstration value, balance and cost. The University of North Dakota had presented two separate bids for dense media separation and mild acid treatment. We suggested a combining of the two to produce two product quality levels and requested a recosting of the bid. The cost of the resulting bid modification was less than the two original bids combined. That option was accepted and included in the package of bids procured.

The results obtained from the five selected contractors are summarized below in Table 5.0-13. A detailed report of their results are given in Appendices G, H, I and J. Since the cleaning services provided by the contractors were not being evaluated competitively, there was no attempt to rate winners or losers. This set of cleaning activities effectively demonstrated that the capability to deep clean this coal by different methods was feasible.

TABLE 5.0-13

ANALYSIS OF CLEAN COALS PREPARED
BY SELECTED CONTRACTORS

Coal Cleaning Contractor	Otica Industries	Virginia Tech.	CODC (EPRI)	UNDEERC
Cleaning Method	Flocculation	Microbubble Column Flotation	Froth Flotation	Heavy Media followed by mild acid wash
Coal Analysis				
Proximate Analysis, (Wt.% dry basis)				
Volatiles Matter	37.43	36.31	37.41	36.66
Fixed Carbon	61.39	62.37	62.37	61.81
Ash	1.18	1.32	1.18	1.53
Sulfur	0.77	0.64	0.70	0.59
Heating Value, Btu/lb	15,199	15,238	15,212	15,054
Ultimate Analysis, (Wt.% dry basis)				
Carbon	86.55	87.07	86.63	86.64
Hydrogen	5.08	5.29	5.27	5.09
Nitrogen	1.49	1.61	1.60	1.55
Ash Fusion Temp. (reducing atmos.)				
Initial	2289	2298	2270	2351
Softening	2375	2410	2395	2447
Fluid	2535	2590	2578	2642
Ash Chemistry, (Wt.% dry basis)				
SiO ₂	38.71	41.99	41.36	41.93
Al ₂ O ₃	27.31	28.08	28.29	28.22
TiO ₂	2.76	1.86	1.90	1.89
Fe ₂ O ₃	16.83	14.93	16.02	14.25
CaO	4.60	4.01	4.12	3.95
MgO	1.31	0.96	0.93	0.99
K ₂ O	2.52	1.53	1.60	1.60
Na ₂ O	1.30	2.09	2.04	2.36
SO ₃	2.51	1.80	1.68	1.88
P ₂ O ₅	0.46	0.33	0.30	0.21
SrO	0.32	0.48	0.39	0.30
BaO	0.12	0.30	0.33	0.32
Mn ₃ O ₄	0.05	0.00	0.00	0.00

5.8.1 Westmoreland Coal Company

Westmoreland Coal Company attempted to clean the Upper Elkhorn #3 coal to a 2% ash level at their Wentz cleaning facility in Wise County, Virginia using their heavy media circuit by lowering the specific gravity of the heavy media. They reported that they were unable to achieve the target ash value. No sample or data is available.

5.8.2 Coal Quality Development Center (EPRI)

The Coal Quality Development Center at Homer City, PA carried out conventional froth flotation cleaning of the coal. The circuit schematic is shown in Figure 5.0-13. As can be seen they achieved a 1.37% ash level but only at a 15% yield. The remainder of the product analyses are given in Table 5.0-13.

5.8.3 University of North Dakota Energy and Environmental Research Center (UNDEERC)

As discussed above, UNDEERC made two proposals, one using a heavy media cyclone and the other acid washing to obtain the low ash coal. In conversations with them it was decided to combine the two, i.e., first clean in the heavy media cyclone followed by an acid wash. Therefore, they would furnish two samples, one cleaned by heavy media separation and one also cleaned by heavy media followed by an acid wash. As can be seen from Table 5.0-13, the heavy media cyclone cleaning gave a 1.64% ash product at a 70% yield while further acid washing gave a 1.41% ash product at a 68% yield. A summary of all tests they conducted is shown in Figure 5.0-14.

5.8.4 Otisca Industries

Otisca used their proprietary T-Process to produce a coal-water slurry. They obtained a 98.6% yield of coal having an ash content of 1.41% (see Table 5.0-13 for complete analysis of the coal). A schematic of their process is shown in Figure 5.0-15. The coal is very finely ground and then isolated from the liberated ash by agglomeration.

5.8.5 Virginia Tech

Virginia Tech employed a microbubble flotation apparatus shown in Figure 5.0-16. They obtained a coal with a 1.29% ash at a 92.9% yield. Complete coal analyses are given in Table 5.0-13.

Figure 5.0-13

EPRI'S FROTH FLOTATION UNIT

Figure 5.0-14

NORTH DAKOTA UNIVERSITY
ENERGY AND ENVIRONMENTAL RESEARCH CENTER

Figure 5.0-15

OTISCA'S FINE COAL CLEANING PROCESS

Figure 5.0-16

VIRGINIA TECH'S
MICROBUBBLE FLOTATION COLUMN

MICROBUBBLE GENERATORS

6.0 TASK 3 - FUEL SUPPLY

6.1 Coals Used for Fuel Preparation

The coals purchased and processed into fuels over the life of the contract are shown in Table 6.0-1. It can be seen that most fuels were prepared from the Upper Elkhorn #3 coal (specifically the Taggart seam coal in Wise County, Virginia). This coal was chosen as the baseline coal during the coal selection process (see Section 5.5). However, because of special needs of certain combustor contractors, it was sometimes necessary to select other coals for fuel preparation. For example, Vortec, who is developing a glass making process, required a slagging coal with ash fusion temperatures lower than those obtained from a deep cleaning Upper Elkhorn #3 coal. Initially they requested a Pittsburgh #8 seam coal. This was purchased, ground and shipped to them. Later, however, it was learned in discussions with AMAX Coal Company that western coals, unlike eastern bituminous coals, would show a decrease in ash fusion temperatures upon cleaning. Therefore, AMAX obtained a subbituminous coal from their Eagle Butte mine and cleaned it by heavy media at a specific gravity of 1.35. This was also sent to Vortec for their trials.

6.2 Deep Cleaning of Candidate Coals

6.2.1 Preparation of Deep Cleaned Upper Elkhorn #3 Coal by Dravo

During the first quarter of the contract, a coal resource evaluation study was conducted to determine the suite of candidate seam coals which could meet the DOE established criteria for the two quality levels of 0.8 and 1.0 lbs ash content and 0.5 and 0.8 lbs of sulfur content per million Btu's. While meeting these goals the prepared fuels would also have to meet both Btu content and ash fusion temperature in accordance to the requests and desires of the combustion contractors. Final definition of the coal selection process resulted in identifying five coal seams, of which drum samples were later obtained and tested. Washability studies and bench-scale flotation tests were performed and concluded with the recommendation that the Upper Elkhorn #3 coal seam could be deep cleaned by semi-conventional technology; meeting all of the requested quality specifications and showing the highest yield potential of 60 percent (see Section 5.0).

In March, 1987, Dravo designed and set up a continuous 300 pound per hour pilot scale grinding and multiple stage deep cleaning froth flotation circuit. Bulk quantities of the Upper Elkhorn #3 feedstock were ordered and processing began immediately. Because the major focus of the EI/Dravo contract was to deliver specification quality fuels to the combustion contractors, and not to research process development, Dravo evaluated the frothing reagent from the bench tests with the pilot circuit, and determined that an equivalent product ash levels could be achieved. Earlier than expected and continuous fuel demands from several of the combustion contractors truncated further testing and forced the pilot circuit into a production mode.

Table 6.0-1

COALS PURCHASED AND USED FOR FUEL PREPARATION

	<u>1987</u>	<u>1988</u>	<u>Fiscal Year 1989</u>	<u>Total</u>
COAL MINED & DELIVERED FOR PROCESSING (Tons)				
Upper Elkhorn #3 Coal, Taggart Seam, Westmoreland Coal Co. Wise County, Virginia	255	314	129	694
Upper Elkhorn #2 Coal, Lower Cedar Grove Seam, Central Coal Co. Virginia Energy Mine No. 1084	22	--	--	22
Beulah-Zap Lignite Coal obtained by the University of North Dakota Energy and Materials Research Center	2	--	--	2
Kemmerer Subbituminous Coal obtained by the University of North Dakota Energy and Materials Research Center	1	--	--	1
Eagle Butte Subbituminous Coal from Amax Coal Company	--	--	--	10
Pittsburgh #8 Seam Coal from Consol's Bailey Mine	--	--	2.2	2.2
Pittsburgh #8 Seam Coal from Consol's Mathies Mine	--	--	3.75	3.75
	<hr/>	<hr/>	<hr/>	<hr/>
Total	280	314	140.95	734.95

In April, 1987, Dravo began processing washed R-O-M coal and had produced nearly 80 tons of deep cleaned fuel feedstock averaging 1.35 percent ash by November, 1987. Throughout the production period, hourly quality control samples were collected from the Dravo pilot circuit to maintain a consistent product quality level, and periodic performance checks were conducted to assure processing efficiency. During the six month period, Dravo made advances in processing capabilities by increasing feed throughput rates from the original 300 to 450 and finally 600 lbs per hour. At the highest rate a decrease in performance efficiency was noted, and later resolved in late October with the addition of an auxiliary set of high energy type (5 cu ft capacity) flotation cells set up to reprocess primary flotation tailings. A pilot production flowsheet showing a material balance and illustrating the final circuit upgrade is exhibited in Figure 6.0-1.

6.2.2 Flotation Reagent Optimization Study

Changes in the contractual program both reducing the required amount of deep cleaned fuels and rescheduling several major shipments until the third and fourth quarter of fiscal year 1988; and an ever increasing concern of project costs, warranted the need and provided a timely opportunity for reevaluating the frother selection and operating parameters for improving recoveries with the pilot deep cleaning circuit.

A written proposal detailing the scope of work necessary to determine if improvements in pilot circuit recovery could be achieved when either using more non-selective frothing reagents and/or changing the physical operating parameters, was submitted by Dravo and approved by Energy International in December, 1987.

The bench-scale flotation test program utilized starvation flotation technology similar to the pilot circuit. Forty-three (43) tests were run using chemical frothers from four reagent categories, (alcohols, alcohol based, glycols, and blends) to establish the yield and quality differential associated with each. Twenty-six of these tests were initially run at standard operating conditions evaluating comparative performance of the nine selected commercially available frothers (generically named reagents A through I and identified in Appendix 5). At these conditions, several of the frothers, representing all but the alcohols, showed minimal yield improvement of less than seven percentage points over the standard reagent used for the production runs. This relates to maximum yield at the 1.10 percent ash level of 47 percent as compared to 39.9 for the comparable production runs. The alcohol frothers due to low solubility could not achieve similar results. In fact, at the 40 percent yield level the alcohol frothers generated a 1.20 percent ash product; consequently shifting the yield ash curve from that observed with the other frothers.

However, the alcohol frother, when used in conjunction with a conditioner such as diesel fuel, improved the yield of clean coal from 40 to 54% at the 1.10% ash level and a yield of 64% at the 1.20% ash level. Further yield improvements were obtained by lowering the feed solids content from 5 to 3%. However, the only way to realize this yield improvement is to cut back on the production rate or by installing an additional 4 cu ft of flotation cell capacity. Complete details of the reagent optimization study are found in Dravo's report no. DECI-8502-02, dated February 1988, entitled "Flotation Reagent Optimization Study for the Dravo Pilot Scale Deep

Figure 6.0-1

DRAVO RESEARCH CENTER SMALL PILOT PLANT-WITH AUXILIARY CELLS

REV. 3

Cleaning Facility". The 120-page report is not appended here but a copy may be obtained as noted in Appendix D.

6.2.3 Other Coals and Coal Cleaning Methods

As discussed in Section 6.2, the majority of the deep cleaned coal used for fuel preparation was the Upper Elkhorn #3 coal cleaned below 2% ash by Dravo in their froth flotation pilot unit. In the original plans the pilot unit was to be replaced by a larger unit which would produce three tons of clean coal per hour. However, after major changes in the fuel supply requirements were made, it was felt that sufficient cleaned coal had already been prepared (76.4 tons between April, 1987 and January, 1988) for the remainder of the contract, and, therefore, the Dravo pilot unit was shut down and Dravo's portion of the contract considered complete.

However, as the contract progressed, several of the combustor contractors required different coals and coal specifications than those obtained from either run-of-mine or deep cleaned Upper Elkhorn #3 coal. These requirements are discussed below.

6.2.3.1 Cleaning of Beulah-Zap Lignite Coal

Avco Research Laboratories of Everett, MA requested 1000 lbs of a deep cleaned micronized lignite coal and 1000 lbs of a 70% solids lignite-water-methanol slurry for evaluation in their combustor. Energy International contracted with the University of North Dakota Energy and Environmental Research Center (UNDEERC) to prepare these fuels from the Beulah-Zap lignite coal seams. The original plan was for AMAX Coal Company of Golden, CO to prepare the low ash coal first by heavy media separation (1.3 specific gravity) followed by an acid wash and then shipment to UNDEERC for drying, micronizing, packaging and shipment to Avco. The first shipment of cleaned coal received by UNDEERC had ash contents ranging from 2.6 to 3.6%, far exceeding the 1.0% or less ash requested by Avco. Follow-up investigations by UNDEERC found that by washing the cleaned coal with deionized water the ash content could be lowered to 1.6% and that an additional acid wash could lower the ash content to 0.6%.

It was at this time, while monitoring the preparation of this fuel, that it was discovered that the acid being used for the chemical cleaning step was nitric acid. Energy International has had in-depth experience with the treatment of lignite and subbituminous coals with nitric acid and knew that the alteration of the coal was so significant that a "representative" fuel was not being prepared. This can be seen in Table 6.0-2 which shows the elemental analysis of the lignite coal before and after physical and chemical cleaning. The significant difference is the large increase in the nitrogen and oxygen contents of the cleaned coal. Experience has shown that nitric acid treatment generally enhances the fuel qualities of the coal. Therefore, work on the preparation of a low ash lignite fuel by nitric acid washing was discontinued. Avco was also notified that the 135 lbs of deep cleaned lignite coal they had already received was not a "typical" lignite fuel. All the nitric acid treated coal was shipped to Energy International for storage and/or disposal.

Table 6.0-2

ELEMENTAL ANALYSIS OF BEULAH-ZAP LIGNITE COAL
BEFORE AND AFTER PHYSICAL AND CHEMICAL CLEANING
(Moisture Free Basis, Weight %)

<u>Analysis</u>	<u>Before Cleaning</u>	<u>After Cleaning</u>
Hydrogen	4.20	4.06
Carbon	65.00	62.68
Nitrogen	0.92	3.08
Sulfur	0.93	0.28
Oxygen	20.10	27.74
Ash	8.85	2.10

Additional efforts to clean the Beulah-Zap lignite were carried out using hydrochloric and/or formic acid with the run-of-mine, 1.4 and 1.3 specific gravity float fractions. With the exception of the nitric acid, the conditions chosen were those recommended by UNDEERC for their nitric acid process. The results of these experiments are shown in Table 6.0-3. It can be seen that a satisfactory low ash (1.3-1.8%) coal can be obtained by substituting hydrochloric acid for nitric acid in the treatment of the 1.3 specific gravity float fraction.

Furthermore, the hydrochloric acid treated products were washed with deionized water until the wash water tested chloride ion free by the silver nitrate test. The chlorine analyses given in Table 6.0-4 show that there was essentially no increase in chlorine in the treated coal over that of the starting coal (1.3 float fraction).

At about this time, at the request of PETC, the work on the preparation of lignite fuels was discontinued. However, near the end of the contract, with PETC's approval, the cleaned lignite fuel that remained was shipped to Avco. This amounted to about 50 lbs of a deep cleaned micronized lignite and 150 lbs of a deep cleaned pulverized lignite.

6.2.3.2 Cleaning of Eagle Butte Subbituminous Coal

In our search to find the coal with the properties required by the University of Tennessee Space Institute (UTSI), that is, a low ash high fusion temperature ($>2500^{\circ}\text{C}$) coal it was learned from AMAX Research and Development Company that, unlike bituminous coals, the ash fusion temperatures of low rank coals will show an increase upon cleaning. Therefore, a sample of the Eagle Butte coal was sink-floated at a specific gravity of 1.4. A sample of the float material was sent to UTSI. UTSI and Energy International approved of its properties so AMAX cleaned and shipped approximately 5 tons of a micronized (96% less than 325 mesh) and approximately one ton of baghouse fines (99.75% less than 325 mesh) to UTSI. The initial deformation temperature was raised to 2450°F from 2365°F . While less an effect than had been predicted from bench-scale work UTSI accepted and used the product.

6.3 Preparation and Delivery of Coal-Water Slurry Fuels

As discussed in Section 5.6 almost all the slurries were provided by OXCE Fuel Company. The deep cleaned wet (5-10% moisture) coal was sent from Dravo to OXCE for processing into slurries. When the slurry specifications called for higher ash or run-of-mine coal the dry unprocessed coal was sent directly from the mine or wash plant to OXCE. Since OXCE claims their manufacturing process to be proprietary, no details of the slurry preparation were revealed. The slurries were then shipped directly from OXCE to the combustor contractors after Energy International ran the quality control characterization studies on a representative sample (see Section 6.5). The same procedures were followed for slurries prepared by AMAX. A listing of all slurry fuels and their deliveries to the combustor contractors is shown in Appendix E.

Table 6.0-3

CHEMICAL DEASHING OF LIGNITE COAL
BUELAH-ZAP LIGNITE

Coal Sample	Weight Coal, gms	Volume Water, ml	Acid ‡	Volume Acid, ml	Reaction Time, hrs	Reaction Temp., C	% Ash	E1 N. B. Ref:
As Received	50	233	HCl	10.8	0.5	80	7.0	002-026-7
15.01% Ash	50	233	HCl	10.8	1.0	80	6.9	002-027-8
	25	115	HCl	10.8	1.0	80	7.1	002-027-9
1.4 float	50	233	HCl	10.8	1.0	80	3.1	002-029-12
9.25% Ash	50	233	HCl	16.2	1.0	80	3.0	002-030-13
1.3 Float	50	233	HCl	5.4	0.5	80	1.7	002-022-1
6.82% Ash	50	233	HCl	5.4	0.5	80	---	
2nd wash	233	233	HCl	5.4	0.5	80	1.3	002-024-1
	50	233	HCl	10.8	0.5	80	1.5	002-024-2
	50	233	HCl	10.8	1.0	80	1.4	002-025-3
	50	233	HCl	10.8	1.0	RT	1.8	002-029-11
	50	233	HCl	10.8	1.0	80	---	
2nd wash	233	233	Formic	8.8	0.5	80	1.4	002-028-10
	50	233	Formic	4.4	0.5	80	2.8	002-023-2
	50	233	Formic	8.8	0.5	80	2.5	002-025-4
	50	233	Formic	8.8	1.0	80	2.5	002-025-5
	50	233	Formic	8.8	0.5	80	---	
2nd wash	233	233	Formic	8.8	0.5	80	1.9	002-026-6

Table 6.0-4

ANALYSES OF LIGNITE COAL SAMPLES

	<u>1.3 Specific Gravity Float</u>	<u>Sample No. 002-025-3*</u>	<u>Sample No. 002-028-10*</u>
PROXIMATE ANALYSIS			
(Dry Basis, Wt %)			
% Ash	6.56	1.43	1.46
% Volatile	58.19	45.88	45.58
% Fixed Carbon	35.25	52.69	52.96
% Sulfur	0.71	0.71	0.72
Btu/lb	10,792	11,465	11,829
ULTIMATE ANALYSIS			
(Dry Basis, Wt %)			
% Carbon	65.38	69.26	69.94
% Hydrogen	4.31	4.48	4.47
% Nitrogen	1.03	1.19	1.21
% Chlorine	0.05	0.07	0.06
% Sulfur	0.71	0.71	0.72
% Oxygen (diff.)	21.96	22.86	22.14

*See Table 6.0-3 for details of sample treatment.

6.4 Preparation and Delivery of Dry Ground Coal Fuel

As discussed in Section 5.7, the majority of the pulverized and micronized dry coals were prepared by Schutz-O'Neil (now Jacobsen, Inc.). Near the end of the contract the services of Minnesota Custom Processing (MCP) were also used to prepare both micronized and pulverized coal. As with the coal-water slurries, samples of the ground material were sent to Energy International for quality control analysis (see Section 6.5). A listing of all dry coal fuels prepared and their deliveries to the combustor contractors are shown in Appendix F.

6.5 Quality Assurance Plan

In order to assure that specification fuel was being produced, and that the coal samples used in the fuel preparation could, if necessary, be traced back to the mine mouth, a quality control plan was established for the fuel supply contract carried out by Energy International, Inc.

The plan developed consists of the following elements:

1. Sample identification
2. Sampling scheme
3. Sample analyses
4. Data logging
5. Sample shipping log

Details of each element are described below.

6.5.1 Sample Identification

The sample identification scheme is shown in Figure 6.0-2 and the identified tables. The sample number consists of 10 characters which identify the coal bed from which the sample came; what type of coal or fuel it was; the origin of the sample, and the sequential sample number. Thus, if a sample is identified as UE3-200-CWF-F it means it is a standard grind coal water fuel (CWF) prepared by OXCE Fuel Company (F) from an Upper Elkhorn #3 coal (UE3) and is the 200th sample shipped under this contract. The three digit number can be considered a serial number. The other possible designations for the sample identification are shown in Tables 6.0-5 and 6.0-6, and 6.0-7.

6.5.2 Sampling Scheme

The points at which samples were taken during the movement of the coal from the mine through the various processing steps until reaching the combustor are shown in Figure 6.0-3. The coal obtained from the mine wash plant was shipped either to Dravo or, in cases where no cleaning was necessary, to the fuel makers. The coal is sampled at this point (sampling point 1). In order to obtain the ultraclean coal required by most of the combustor contractors the coal is cleaned by Dravo by froth flotation. Hourly samples were taken for quality control of the process (sampling point 2).

Figure 6.0-2

SAMPLE IDENTIFICATION SCHEME

	<u>xxx</u>	<u>xxx</u>	<u>xxx</u>	<u>x</u>
	:	:	:	:
	:	:	:	:
Coal Bed ID-----:	:	:	:	:
(three letter designation,	:	:	:	:
see Table 6.0-5)	:	:	:	:
	:	:	:	:
	:	:	:	:
Sequential Numbers-----:	:	:	:	:
(three digit numbers which	:	:	:	:
increase by one for	:	:	:	:
successive samples)	:	:	:	:
	:	:	:	:
	:	:	:	:
Coal or Fuel Form-----:	:	:	:	:
(three letter designation	:	:	:	:
see Table 6.0-6)	:	:	:	:
	:	:	:	:
Sample Origin-----:	:	:	:	:
(one letter designation	:	:	:	:
see Table 6.0-7)	:	:	:	:

Table 6.0-5

COAL BED ABBREVIATIONS

<u>Abbreviation</u>	<u>Coal Name</u>
UE1	Upper Elkhorn #1
UE2	Upper Elkhorn #2
UE3	Upper Elkhorn #3
LEL	Lower Elkhorn
CBD	Coal Basin D
ELC	Elk Creek
LBT	Lower Bakerstown
UFR	Upper Freeport
UBN	Upper Banner
WYD	Wyodak
CBE	Coal Basin E
BLC	Black Creek
ANW	Anderson Wyodak
LR3	Laramie #3
2GS	#3 Gas
BZP	Beulah-Zap
ADA	Adaville

Table 6.0-6

COAL OR FUEL FORM ABBREVIATIONS

<u>Abbreviation</u>	<u>Meaning</u>
ROM	Run of Mine
WRM	Washed ROM
PCO	Pulverized Coal
DCC	Deep Cleaned Coal
MCO	Micronized Coal
CWF	Standard Grind Coal-Water Fuel
MCW	Micronized Grind Coal-Water Fuel

Table 6.0-7

SAMPLE ORIGIN DESIGNATION

<u>Abbreviation</u>	<u>Meaning</u>
A	Coal supplier
B	Beneficiator
C	Size Reduction Firm
D	Dravo
E	Energy International
F	OXCE Fuel Company
G	AMAX
N	University of North Dakota Energy Research
P	Penn Rillton - Pulverizer
S	Schutz-O'Neill - Micronizer

Figure 6.0-3

SAMPLING SCHEME

(#) SAMPLING POINTS

Generally only ash values were obtained. For shipment of the deep cleaned coal to OXCE for coal-water fuel preparation, the wet filter cake was removed batchwise and placed in drums so it was impossible to obtain a representative sample of the deep cleaned coal at the cleaning plant. A representative coal analysis was obtained, however, by taking a sample of the finished slurry fuel and isolating the coal from it and submitting it for analyses (sampling point 6). Meanwhile, OXCE sampled the slurry for themselves (sampling point 3) and determined certain physical and rheological properties. An additional representative sample of the slurry was taken by OXCE (sampling point 4) and sent to Energy International to confirm the analyses and to carry out storage stability tests. A portion of this sample was sent to Dravo for the coal isolation and analysis as described earlier. Finally, if the deep cleaned coal was used for preparation of pulverized or micronized coal a representative sample of the fuel was obtained by Dravo from the micronizer (sampling point 5) and submitted for analyses.

This sampling procedure along with the sample identification scheme should insure that the right coal is obtained and processed to obtain the correct specifications for the individual needs of each combustor.

6.5.3 Sample Analysis

The samples obtained at the various points of the process were analyzed as described below.

Sample No. 1 - A representative sample of each lot of coal purchased was obtained by Dravo or Energy International and submitted for the following analyses:

- Proximate Analysis
- Ultimate Analysis
- Ash Fusion Temperatures
- Ash Chemistry
- Hardgrove Grindability
- Free Swelling Index

Sample No. 2 - Hourly samples taken for ash analysis during the cleaning process as a means of process control.

Sample No. 3 - This sample was taken for analysis by the slurry manufacturer, in this case, OXCE Fuel Company. They carried out and reported the following analyses:

- % Solids
- Density
- pH
- Particle Size Distribution
- Viscosity as a Function of Shear Rate
- Temperature Stability

Sample No. 4 - A sample of slurry was sent to Energy International where a rapid analysis was carried out to confirm the analysis furnished by OXCE. In addition, a long-term (two month) storage stability test was carried out. This consisted of determining the amount and quality (hard pack, soft pack, etc.) of any settlement which occurred in the slurry. The other slurry analyses performed by EI were:

- % Solids
- Density
- pH
- Screen Analysis
- Particle Size Distribution
- Viscosities at 100 and 200 sec⁻¹ and 70°F

Sample No. 5 - A sample of the micronized coal was obtained from the pulverizer by Dravo or Energy International. If the fuel was prepared from a deeply cleaned coal then a sample was submitted for the following analyses:

- Proximate
- Ultimate
- Ash Fusion Temperature
- Ash Chemistry
- Particle Size Distribution
- Free Swelling Index

If the coal was a washed run-of-mine coal (i.e., not deep cleaned) then only a particle size distribution analysis was carried out. The parent coal analyses sufficed for the fuel analysis.

Sample No. 6 - If the coal used in the fuel was deep cleaned, a sample of the slurry received by Energy International was sent to Dravo for isolation of the coal and its analysis. The analyses carried out by Dravo and later by Energy International were:

- Proximate
- Ultimate
- Ash Fusion Temperature
- Ash Chemistry
- Free Swelling Index

As before, if washed run-of-mine coal was used for the fuel preparation then the parent coal analyses was sufficient for the fuel analysis.

6.5.4 Data Logging

All the analytical data obtained on all coals and fuels are sent to Energy International. A data sheet is then compiled for each sample. Examples of the data sheets and the information contained therein are shown in Tables 6.0-8, 6.0-9, and 6.0-10. Table 6.0-8 is the data sheet for the coal samples and Tables 6.0-9 and 6.0-10 for the slurry fuels and the solid micronized (or pulverized) coals, respectively. The data sheets prepared for all samples shipped are given in Appendix K.

-74-
Table 6.0-8

file:coalid	Sample Identification No.:	xxx-xxx-xxx-x	No.:
SAMPLE INFORMATION		PROXIMATE ANALYSIS	
Bed Name:	Moisture		%
Bed No.:	Volatile Matter		%
Local Name:	Fixed Carbon		%
Mining Co.:	Ash		%
Mine Name:	Sulfur		%
Wash Plant:	Btu/lb		
State:	ULTIMATE ANALYSIS		
County:	Carbon		%
Amount:	Hydrogen		%
Date Shpd:	Nitrogen		%
ASH CHEMISTRY		ASH FUSION TEMP.: REDUCING	
SiO2	%	Initial	deg. F
Al2O3	%	Softening	deg. F
TiO2	%	Fluid	deg. F
Fe2O3	%		
CaO	%	FREE SWELLING INDEX:	
MgO	%		
K2O	%	HARDGROVE GRINDABILITY:	
Na2O	%		
SO3	%	FORMS OF SULFUR	
P2O5	%	Pyritic	%
SrO	%	Sulfate	%
BaO	%	Organic (diff)	%
Mn3O4	%		
B/A Ratio:			
T-250 TEMP.	deg. F		

Table 6.0-9

file:cwfid Sample Identification No.: xxx-xxx-xxx-x No.:xxx

Sample
Description

Parent

Coal I.D.: xxx-xxx-xxx-x

Bed Name:

Bed No.:

Local Name:

Mining Co.:

Mine Name:

Wash Plant:

State:

County:

PROXIMATE ANALYSIS

Moisture %

Volatile Matter %

Fixed Carbon %

Ash %

Sulfur %

Btu/lb

Btu/lb

(as Received)

ULTIMATE ANALYSIS

Carbon %

Hydrogen %

Nitrogen %

ASH CHEMISTRY

ASH FUSION: REDUCING

SiO2 %

Al2O3 %

TiO2 %

Fe2O3 %

CaO %

MgO %

K2O %

Na2O %

SO3 %

P2O5 %

SrO %

BaO %

Mn3O4 %

Initial deg. F

Softening deg. F

Fluid deg. F

FREE SWELLING INDEX

HARDGROVE GRINDABILITY

FORMS OF SULFUR

Pyritic %

Sulfate %

Organic (diff) %

Base Acid Ratio:

T-250 TEMP. deg. F

Coal Water Fuel Analysis

% Solids = Viscosity = cps @100/sec, 70 deg F

Density =

pH = Particle Size Analysis

% Sulfur =

% Ash =

Wt. % <100 mesh =

Mean Part. Size = um

From:

Amount:

Date:

To:

Table 6.0-10

file:scfid Sample Identification No.: xxx-xxx-xxx-x No.:

Sample
Description

Parent

Coal I.D.: xxx-xxx-xxx-x

Bed Name:

Bed No.:

Local Name:

Mining Co.:

Mine Name:

Wash Plant:

State:

County:

PROXIMATE ANALYSIS

Moisture %

Volatile Matter %

Fixed Carbon %

Ash %

Sulfur %

Btu/lb

ULTIMATE ANALYSIS

Carbon %

Hydrogen %

Nitrogen %

ASH CHEMISTRY

SiO2 %

Al2O3 %

TiO2 %

Fe2O3 %

CaO %

MgO %

K2O %

Na2O %

SO3 %

P2O5 %

SrO %

BaO %

Mn3O4 %

ASH FUSION: REDUCING

Initial deg. f

Softening deg. f

Fluid deg. f

FREE SWELLING INDEX

HARDGROVE GRINDABILITY

SULFUR FORMS

Pyritic %

Sulfate %

Organic (diff) %

Base Acid Ratio:

T-250 TEMP. deg. F

Solid Coal Fuel Analysis

Particle Size Distribution

MICRO-TRAC Analysis

Mean Particle Diameter um

%<100 mesh(149 um)

%<400 mesh(38 um)

From:

Amount:

Date:

To:

6.5.5 Sample Shipment Log

Finally, a master log of all sample shipments was kept. The log identifies each shipment by its sample identification number, the date and amount shipped, from and to whom shipped, along with Energy International's purchase order number covering the transaction. The sample shipment log is shown in Appendix L. This format, which is updated weekly, allows the Manager to determine the sample shipment status at a glance and prevents the assignment of the same serial number to two different samples.

7.0 CONTRACT ACTIVITIES UNDER MODIFICATION #A014

7.1 Introduction

Near the conclusion of the earlier contract term, the Department of Energy identified the need for additional premium fuels for use by its combustion contractors and in-house testing projects. The preparation and delivery of these additional fuels is the subject of Table 7.0-1 "Fuel Specifications" which is the basis for Modification #A014. This work was performed during May 1990 to August 1991. Fuel specifications were modified during this period in order to accommodate coal and fuel availabilities while still satisfying the needs of the combustor development projects.

The activities conducted under Modification #A014 are reported in Section 7.0 and Appendix M. These activities are reported separately from the fuel supply activities conducted prior to the Modification #A014, which are reported in Sections 1.0 through 6.0 and Appendices A through L. Discussion of these added deliveries and the coal fuel data sheets and delivery schedules are provided by these additional sections to the original version of the Final Report.

7.2 Specifications

Initial specifications for the several fuels delivered during this extended period of contract performance were provided with the contract modification by PETC. These specifications were based on discussions with the users of the fuels and are shown in Table 7.0-1. During the period of performance, the specific requirements for the fuels were modified as appropriate to meet the changing needs of the users, to meet the budget limitations, and to take advantage of the availability of cleaning and preparation services through coordination with schedules. Thus, some of the specifications were changed to accommodate these interests. These changes in specifications were in all cases minor and consistent with the specific objectives of the individual projects. The properties of the delivered fuel products are in the data sheets in Appendix M. The coal cleaning, fuel preparation processing and changes in specifications are discussed in Section 7.6.

7.3 Objectives

The objectives of Modification #A014 are the same as those for Task 3 because this additional work is an extension of Task 3.

7.4 Fuel Properties

Analytical data sheets for these delivered coal fuels and their source coals are in Appendix M.

7.5 Fuel Deliveries and Quantities

Fuel delivery information is found in Appendix M.

Table 7.0-1

FUEL SPECIFICATIONS (1)

(Contract Modification #A014,
May 1990 - August 1991)

SCOPE OF WORK

The Scope of Work (Section 3.0) was modified to include the following coal-based fuels:

Fuel No.	1	2	3	4	5	6
Coal Type	HVAB	Upper Elkhorn	Upper Elkhorn	Upper Elkhorn	HVAB	HVAB
Fuel Form	CWF	Pulverized	Pulverized	Pulverized	(4)	Pulverized
Ash, %	< 5.0	6-10	3.5-4.5	≤ 2.0	≤ 2.0	7-10
Sulfur, %	2.0-2.5	< 1	< 1	< 1	< 2	< 1
Particle Size Range, μ	70% < 44	70% < 74	70% < 74	70% < 74	70% < 44	70% < 74
Ash Soft Temp., °F	99% < 200	> 2400	> 2400	> 2400	> 2400	T250 < 2500° F
Volatile Matter, %	≥ 30	≥ 30	≥ 30	≥ 30	≥ 30	≥ 35
Quantities, tons dry	1.5	1	1	1	2	100
Delivery Location	Waltham, MA	Pgh., PA	Pgh., PA	Pgh., PA	Pgh., PA	Baltimore, MD
Packaging Container	Drums	Drums	Drums	Drums	Drums	2-ton bins (5)
Solids Loading, wt% -1	> 55	N/A	N/A	N/A	> 55	N/A
Viscosity at 100 sec -1	200-400cp	N/A	N/A	N/A	200-400cp	N/A

Notes:

- (1) Energy International, Inc. should prepare the listed fuels, using to the extent possible coals that are in the inventory and being stored under the contract. In addition, all deliveries shall be accompanied by a material data safety sheet.
- (2) Fuels 2, 3, and 4 shall incorporate the same parent coal that was used by the Advanced Combustion Program contractors. Delivery shall be made to: West Penn Warehousing, Inc., Fourth and Main Street, Belle Vernon, PA 15012.
- (3) Fuel 5 shall be obtained from an advanced cleaning process, e.g. VPI's microbubble flotation; deliver to West Penn Warehousing, Inc.
- (4) One ton will be prepared as CWF; the other ton will be the product of the advanced cleaning process.
- (5) The Contractor for utilizing Fuel 6 does not have storage capabilities; these bins or similar containers are preferred to minimize packaging costs.

7.6 Discussion

Each of the fuels that were to be delivered under this modification to the contract was a singular, one-time-only fuel requirement. As such, the fuels were not generally available for procurement and required individual arrangements to process or procure. Thus, much of the work involved was to determine the options available to meet the user's needs and then to modify the specifications to meet those interests. This involved selections of the coal, processing, packaging, and scheduling.

Fuel #1

Fuel #1 was requested to be a high sulfur, low ash coal-water fuel to be used in testing of an emissions control system by Tecogen of Waltham, MA. The combustor being used is not designed to accommodate large amounts of ash and so it was desired to keep the ash content as low as possible. This was consistent with the commercial targets for this combustion system. However, since the test operating time would be limited by the ash collection capacity, this necessitated that the highest reasonable sulfur loading be put on the sulfur control component of the emission control system. Thus, the project sought a fuel that was both low in ash and high in sulfur content.

It was recognized that the dual requirement of low ash and high sulfur would impose conflicting criteria on the selection of the coal to be used. It was further necessary to be able to prepare a coal-water fuel without extensive formulation or processing work. To attain the low ash level of less than 5% ash, it was necessary to physically clean the coal. For most of the logical candidates for meeting these requirements, this meant that the physical cleaning would remove virtually all of the sulfur-containing pyrite in the process of ash reduction. Therefore, it was necessary to identify a coal with a particularly high level of organic sulfur so that the desired target level of 2.0 to 2.5% sulfur would be attained. It was decided to use an Illinois Basin coal.

Energy International was aware that Amax R&D had prepared some coal-water fuel from an Illinois #6 coal produced at Amax's Delta mine. Amax had a quantity of the needed coal available at their facility that had already been cleaned. Some of this coal had previously been made into coal-water fuel; so, the formulation and preparation work could be minimized. Energy International issued a purchase order to Amax to prepare and deliver the requested fuel.

The request from Tecogen that was included in the contract modification specifications called for the delivery of 1.5 tons of dry coal in a coal-water fuel with solids loading greater than 55%. Thus, this would have meant that the delivered quantity would be about 580-600 gallons of CWF product. Amax informed us that they did not have a sufficient quantity of cleaned coal to meet this delivery quantity. They had a small amount of the same coal that was not as low in ash, and it could be blended. After dis-

cussions among PETC, EI, and Tecogen, it was agreed that Amax would deliver 370 gallons of CWF at a solids loading of less than the target of 55% and ash content slightly higher than the target of 5% (53.49% solids and 6.74% ash actual).

Fuels #2, 3, & 4

These three fuels were all to be dry pulverized coal of different ash contents and derived from the same base coal, the Upper Elkhorn #3 baseline coal that had been used as the reference coal for deliveries throughout the contract. This would enable PETC to evaluate the effects of different ash levels in combustion testing with a well established performance base in their in-house testing program. The initial request was for one ton of each of three different ash levels. Satisfying this request in a normal manner would have likely been very expensive. This coal can only be obtained in truck-load quantities (23 tons) and would thus require handling in a larger facility. Cleaning the coal to different ash level specifications in any of the advanced coal cleaning facilities would have required preliminary testing to establish production conditions and would be conducted in reasonably small production rates. Wet processing would have necessitated drying the product and pulverizing to meet the delivery specifications. Cleaning the coal at the CQ Inc. facilities in Homer City, PA would require use of the 20 ton/hr circuit and operating at different run conditions.

Fortunately, it was recognized that satisfying these fuel requests could be met in conjunction with a coal cleaning requirement that Energy International was anticipating to be needed for a separate contract with Arthur D. Little, Inc. It was anticipated that ADL would be needing a large quantity of this coal cleaned to less than 2% ash for the preparation of coal-water fuel for their coal-fueled diesel engine project. It was to be cleaned from the nominal 6% ash feed coal from the Wentz Preparation Plant of Westmoreland Coal Company. Thus, it was feasible to wait until the CWF requirement for ADL was scheduled and then use (a) the low-ash cleaned coal, (b) the high-ash feed coal, and (c) a blended product of the two. The coal products of different ash levels were then sent to Penn-Rillton to be pulverized to utility grind specification and delivered to the PETC warehouse. PETC had agreed to receiving a total of three tons of coal fuel of at least two different ash levels. They could then use and blend the drums of coal as needed. The coal delivered to PETC included the high ash feed coal, some of the cleanest coal at about 1.7% ash, and some blended coal.

Fuel #5

The fuel requested for delivery #5 was to be a coal cleaned by an advanced physical coal cleaning method, such as the microbubble column flotation technology being developed by Virginia Tech. The purpose for testing this specific fuel was to compare the combustion characteristics of the deeply-cleaned coal with the parent coal. The PETC in-house combustion testing project had an agreement with Consolidation Coal Company to conduct

some joint testing and evaluations, and Consol was supplying the coal for that joint testing. It was decided to use the coal from that joint testing program (a Pittsburgh #8 coal from the Blacksville operations of Consol) as the parent coal.

Arrangements were made with Virginia Tech to clean this coal in their pilot plant column flotation unit. The clean coal product from the column flotation was then centrifuged at the University to about 60% solids and then was shipped to Allis Minerals Systems to be thermally dried to final product moisture specifications. This processing sequence made it necessary that the coal be ground to the final product sizing prior to the column flotation cleaning step and then maintained at that size distribution throughout the remaining processing.

The Pittsburgh #8 coal is not known to be a coal that is easily deep-cleaned to very low ash and sulfur levels. The coal has a substantial organic sulfur content that cannot be reduced by physical cleaning methods. In the cleaning step, it should be noted from the data sheets in Appendix M that there was some reduction of both sulfur and ash. Sulfur was reduced from 2.57% to 1.97% with most of this being reduction of the pyritic sulfur. The ash was reduced from 8.22% to 3.88%. The ash reduction was not preferential toward any particular ash forming constituent. The ash composition analysis indicates that the ash from the cleaned product is nearly identical to the ash from the parent coal, just less of it.

Fuel #6

MTCI requested shipment of 100 tons of a typical eastern bituminous coal with good slagging characteristics. The request included a specification that the coal be shipped in 1 to 2 ton bins for convenience of storage at their facility, and for lifting and discharge into the feed tank.

This particular request had two notable concerns that needed to be resolved, and this was accomplished to the satisfaction of the fuel user, MTCI. The first concern was with the selection of a coal that met the user's coal characteristics specifications and did not require special processing in order to meet the particle size specifications. Coal pulverized to utility grind is not a product that is usually found to be available for commercial sale and distribution. Disrupting the in-line pulverizers at a typical commercial installation to obtain this quantity did not seem to be economically viable and would have created a packaging problem. The quantity of 100 tons was too large to be supplied by the usual companies that can provide size reduction services for research and development quantities and would have been too expensive if produced in that mode. The second concern was with the request for delivery in bins. Those bins were not available in sufficient quantity to be borrowed or rented. Purchase of bins for this one-time use would have been prohibitively expensive and was not considered.

By being flexible in both the coal specifications and packaging, MTCI was able to accept a commercially available coal product that was a pulverized typical Pittsburgh #8 coal and packaged in 100 pound plasticlined paper sacks. This option made it practical to deliver the quantities needed with a schedule suited to the needs of MTCI's testing operations. It could be purchased and delivered as needed. MTCI found that their fuel handling

system could readily handle the sacks by lifting them to the feed tank and slitting the bag on a sharp edge to discharge the coal into the system.

The Pittsburgh #8 coal available through this source is relatively low in both ash and sulfur content for commercially available quantities of this type of coal. It's sulfur content of about 1.6% was substantially higher than that typical of eastern low sulfur coals, but much lower than that typical of so-called high sulfur coals available in the northern Appalachian region. This was higher than MTCL's requested specification of less than 1% sulfur. Being a cleaned coal, the ash level was also less than the MTCL specification level of 7-10% ash. MTCL agreed to accept this coal after discussing the alternatives that would be available.

8.0 RESULTS AND CONCLUSIONS

The results of the efforts of this contract have shown that, with the proper coal selection, the clean coal fuels required for DOE's combustor development program could be produced by conventional coal cleaning technologies. While the majority of the deep cleaned coal used in this program was prepared by conventional froth flotation, it was demonstrated near the end of the contract that other methods, such as heavy media separation, microbubble column flotation, selective agglomeration and heavy media cyclones were also able to prepare low ash (1.2-1.5%) coal. With the deep cleaned coals as well as the higher ash (mine washed) coal it was possible to prepare both utility grind (149 micron top size) and micronized (44 micron top size) coal-water slurries as well as utility grind and micronized dry coal fuels. The timely delivery of fuels with such diverse specifications aided in the progress of the combustor development program. The specific needs and specifications of the individual contractors were met.

During the resource evaluation and coal selection process, it was found that it was possible to select candidate coals representative of extensive coal resources that extend over a four state region. Therefore, the development of low ash, low sulfur coal-based fuels for combustion applications should not depend upon a specific coal or coal source. Suitable coals should be widely available.

TASK 1 - TOPICAL REPORT

ANALYSIS OF FUEL NEEDS
AND
SELECTION OF CANDIDATE COALS

Prepared For:

U.S. Department of Energy
Pittsburgh Energy Technology Center

Under Contract No. DE-AC22-86 PC90258
"Characterization & Supply of Coal Based Fuels"

ENERGY INTERNATIONAL, INC.
135 William Pitt Way
Pittsburgh, PA 15238
Report No. 0587-008
July, 1987

"Characterization & Supply of Coal Based Fuels"

Task 1 - Topical Report "Analysis of Fuel Needs and Selection of Candidate Coals"

TABLE OF CONTENTS

1.0	INTRODUCTION & BACKGROUND	1
2.0	OBJECTIVES AND SCOPE OF WORK	3
2.1	Contract Objectives	3
2.2	Contract Scope of Work	3
2.3	Task 1 Objective	3
2.4	Task 1 Approach	4
3.0	EXECUTIVE SUMMARY	6
4.0	RESOURCE AND MARKET ASSESSMENTS	7
4.1	Discussion of U.S. Coal Resource Base	7
4.2	Discussion of Market Assessment Approach	10
4.3	Assessment of Market Needs	12
5.0	COAL RESOURCE EVALUATION	23
5.1	Background	23
5.2	Combustor Types	23
5.3	Fuel Specifications	23
5.4	Discussion of Selection Factors	25
5.4.1	Washability Characteristics	25
5.4.2	Coal Quality Analysis	27
5.4.3	Supplemental Geological Publication	27
5.4.4	Availability/Coal Resource Data	30
5.4.5	Combustibility and Ash Slagging	31
5.4.6	Transportation Considerations	35
5.4.7	Slurryability of CLM	38
5.4.8	Flowability of Dry Dense Powder	38
5.5	Selection of Candidate Coals	39
5.5.1	Selection Criteria	39
5.5.2	Resource Evaluation and Recommendation Procedures	40

5.6	Resource Evaluation Conclusions	42
5.6.1	RCLI	42
5.6.2	Slagging Combustor Fuels	42
6.0	CANDIDATE COALS	44
7.0	FUEL SPECIFICATIONS & SUPPLY	49
APPENDIX A		51

LIST OF TABLES

<u>Table No.</u>	<u>Title</u>	<u>Page No</u>
4.1	Summary of U.S. Coal Resources	9
4.2	Potential Market for Coal-Based Fuels	11
4.3	Representative CLM Plant	13
4.4	Estimating Ratios for CLM Plants	14
4.5	Maximum Coal Use Potential - MAXCUP	16
4.6	Market Implications - MAXCUP	17
4.7	Distribution of Fuel Plants Maximum Coal Use Potential - MAXCUP	18
4.8	Reduced Coal Use Potential - REDCUP	20
4.9	Market Implications - REDCUP	21
4.10	Distribution of Fuel Plants Reduced Coal Use Potential - REDCUP	22
5.1	Performance Goals for Coal-Base Residential, Commercial and Industrial Boilers Applicable to Coal Selection	24
5.2	Potential Fuel Candidates for Commercial/Industrial Application (<1.5% Ash, Compliance)	29
5.3	Supplemental List of Seams Meeting Slagging Quality Specifications	31
5.4	Potential Coals for Slagging Type Combustors	32
5.5	Coal Fuel Ratio	34
5.6	Current Freight Charges	37
6.1	Candidate Coals for Residential, Commercial, and Light Industrial Markets	45
6.2	Candidate Coals for Slagging Combustors	46
7.1	Specifications for Solid Fuel	50
7.2	Specifications for Coal Water Fuels	50

LIST OF FIGURES

<u>Figure No.</u>	<u>Title</u>	<u>Page No.</u>
4.1	Coal-Bearing Areas of the United States	8
5.1	Acceptable Coal Ash Levels for Slagging Combustors	26
5.2	Potential Low Ash Coals for Residential Application	28
5.3	Freight Charges and Coal Pricing	36

1.0 INTRODUCTION & BACKGROUND

Under the Department of Energy's Advanced Combustor Technology Program, approximately 13 combustor contractors are developing combustion systems (during 1987-1989) for use in residential, commercial, light industrial and industrial retrofit markets. Sufficient quantities of well-characterized, coal-based fuels possessing specific, appropriate specifications are required by the contractors. Fuels may be dry pulverized coal or coal liquid fuels. In support of these equipment development efforts, the team of Energy International and Dravo Engineers (under DOE Contract No. DE-AC22-86 PC90258) will provide such fuels.

Nearly a third of the total energy use in the U.S. is in the residential, commercial, and light industrial sectors. Of this, about half of the energy is supplied by the direct consumption (not including electricity) of conventional oil and gas resources. Thus, there is a significant energy use component for which coal is not currently a viable user option.

For coal to significantly penetrate this important market sector, it must be demonstrated that:

- Premium coal-based fuels can be prepared and combusted in low maintenance, automatic systems to which such users are accustomed, i.e., be direct replacement of conventional fuels and require only simple installation changes.
- Advanced coal fuel combustion systems can effectively combust coal fuels while meeting economic, environmental, and performance standards.
- Coal fuels, combustion systems and service support are well matched, reliable and are anticipated to be available over the projected lifetime of the installations.

The key to development of fuel and combustor technologies for future application to the use of premium coal-based fuels in the residential, commercial and light industrial energy use sectors is to make available representative coal fuels. Current technologies in early development stages offer the promise to meet the market, performance and environmental acceptability that are expected to be required. However, the developmental testing of advanced combustion equipment systems requires fuels for testing; test experience and performance measures are needed to identify cost competitiveness in the market and specific market niches for early commercialization; and, commercial market opportunities are needed to justify and specify the development and installation of advanced fuels facilities.

The capability to economically produce significant quantities cannot be supported in the current economic and energy use situation. Once these pieces of experience and information begin to fall into place, the market driven needs will more clearly identify the suite of coals that will satisfy the markets and the performance requirements (cost, maintenance, energy efficiency, environmental). For now, it is important to provide suf-

ficient quantities of fuels to enable development testing to proceed. While the definitions of market and performance are not finalized, it is possible to make use of current understanding of coal resources, markets, and combustor requirements to make reasonable selections of coals for fuels representative of future advanced fuels. With selected coals, current versions of advanced premium coal-based fuels can be prepared using conventional beneficiation methods along with special processing that would not be technically or economically viable in commercial operations. On this basis, coal-based fuels for advanced combustor testing will be provided through this supply program.

The analysis of fuels needs, selection of candidate coals, characterization and supply in this contract are to be accomplished with the above in mind. The best choices of those available will be made based upon the available information, coal and processes. This will at least provide the developmental test fuels that will enable the DOE-PETC advanced combustion and fuels program to move forward. It is expected that following the fuels and combustor development activities that this supply contract will support, additional or optional candidate coals will become evident based on the new experience. In the meantime, these coal fuels will enable the program to proceed.

2.0 OBJECTIVES AND SCOPE OF WORK

2.1 Contract Objectives

Contract objectives are as follows:

- Develop fuel specifications to serve combustor requirements
- Select coals having appropriate compositional and quality characteristics as well as an economically attractive reserve base
- Provide quality assurance for parent coals and fuel forms
- Deliver premium coal based fuels to combustor developers as needed for their contract work

2.2 Contract Scope of Work

Energy International/Dravo will perform the following:

- From information both obtained from the combustor PRDA and received from combustor contractors, develop fuel specifications and schedule.
- Using published reports and databases, perform a market assessment and a resource assessment in order to identify acceptable coals within reasonable proximity to markets. In other words, determine the availability and applicability of a wide range of coals in order to produce premium coal-based fuels for specific markets.
- From all coal ranks and all domestic resources select eight coals which satisfy the requirements of combustion systems being developed.
- Procure and produce premium coals having the ability to be processed to contain <1% ash and <0.8% sulfur.
- Procure coals and produce coal liquid mixtures or dry pulverized coal and deliver these premium fuels to combustor contractors.

2.3 Task 1 Objectives

The objectives of Task 1, the Analysis of Fuels Needs, are as follows:

- To provide analyses, information and evaluation of coal resources, coal properties, and market opportunities to support the selection of coals for characterization, processing and supply.

- To assure that coals used in developmental testing are representative of future potential coal used in those applications and are:
 - Available as U.S. domestic resource in sufficient quantity
 - Geographically proximate to the regional markets
 - Capable of being processed into premium coal-based fuels that have the properties to satisfy the combustor needs and market constraints (such as environmental)
- To evaluate, interpret and assess the available information on coal reserves, market opportunities, performance requirements, environmental acceptability, coal properties and specific characteristics to provide guidance in the selection of candidate coals for characterization and supply for developmental testing of advanced combustors for residential, commercial and light industrial applications.
- To collect, review and evaluate information about specific, currently available coals that can be procured from existing mining operations to provide contracted quantities of developmental test fuels that satisfy the reserves, market, geographic, property, performance and environmental criteria.
- To recommend candidate coals and then select specific coals to be purchased, processed into coal-based premium fuels, and supplied to DOE users.
- To coordinate the performance requirements of combustor developers under DOE-PETC contract and in-house efforts with the selection and supply of coals.

2.4 Task 1 Approach

The approach used for the Analysis of Fuels Needs (Task 1) focuses on: The premises reviewed in the Introduction and Background section; the stated task objectives; and, the need to use currently available information, coals and processing in order to supply actual coal fuels meeting representative specifications and in sufficient quantities to satisfy developmental testing needs. Therefore, the approach is to employ the results of previous DOE-sponsored studies, including broad-scale market assessments, national coal data compilations, current mining reserves and records, progress reports on fuels and combustion system requirements. This will be supplemented as appropriate by other documents from state-sponsored studies and commercial publications.

The approach for the task is to effectively use available coal resources and information based on previous DOE studies and experience and the good, professional judgements of the project participants. New ways of interpreting and assessing this information have been found and are discussed in the text. The focus is to provide fuels representative of future needs in the current timeframe as best available.

Since the supply contract will of necessity use coal from existing mining operations and existing process technology, the approach of Task 1 uses currently available information. While it is recognized that other candidate coals may eventually prove to be more appropriate to later developed technologies, this analysis is directed to use available information and sources. The most likely markets, performance requirements and coal selections are the basis for this analysis. For example, washability data is used as an important discriminating criteria in coal selection even though process specifications will undoubtedly push the processing beyond the levels of ash and sulfur reduction characterized by the washability data. Some potential candidates which don't meet the best category on the basis of washability data may later prove to be reasonable options. This can't be determined until more definitive criteria are developed. Similarly, additional cost estimation of selling price for coal fuels and more detailed market studies could lead to other market driven candidates.

3.0 EXECUTIVE SUMMARY

Under the Department of Energy's Advanced Combustor Technology Program, approximately 11 combustor contractors (under 13 contracts) are developing combustion systems (during 1987-1989) for use in residential, commercial, light industrial and industrial retrofit markets. Sufficient quantities of well-characterized, coal-based fuels possessing specific, appropriate specifications are required by the contractors. Fuels may be dry pulverized coal or coal liquid fuels. In support of these equipment development efforts, the team of Energy International and Dravo Engineers (under DOE Contract No. DE-AC22-86 PC90258) will provide such fuels.

The major coal fields of the U.S. were reviewed to correlate with the market needs analysis. Prior to the detailed coal resource evaluation, the locations of fields with major reserves of low sulfur coal potentially amenable to premium coal-based fuels specifications were identified.

An estimate of the total potential annual demand of between 3 and 6 Quads (or roughly 100 to 200 million tons per year of dry beneficiated coal) was provided by PETC on the basis of previous market studies. To provide a realistic focus of the market assessment information to aid in the selection of coals for this project, a three-tiered market demand assessment was adapted from the previous studies. With the assistance of representative coal fuel plants estimating factors, a reduced scope market potential was identified. This market need of over 0.5 Quads can be supplied by about 9 fuel process plants focused to satisfy the major component of that demand, which is the residential demand of the Northeast and Midwest. Therefore, the coals selected for developmental testing will need to satisfy the most stringent fuel requirements and stretch the fuel processing (deep cleaning) capabilities beyond the current state-of-the-art.

Using existing coal database information on reserves, properties and washabilities, selective searches of the coal resource data were conducted to identify candidate coals meeting the stringent fuel requirements. One set of candidates for the residential, commercial, and light industrial was prepared. That list was comprised of 4 coal beds from the Southern Appalachian low-sulfur coal fields and one coal bed in Colorado. A more extensive list of candidates for slagging coals was identified and included potential candidates from all major coal provinces.

The combustion contractors sponsored in DOE programs were contacted to identify their fuel specifications requirements and anticipated fuel delivery requirements (schedule and quantities). The results of that survey show that fuel specifications are consistent with initial contract plans but quantities are greater; results are tabulated later in this report.

4.0 RESOURCE AND MARKET ASSESSMENTS

4.1 Discussion of U.S. Coal Resource Base

The major coal fields of the U.S., as shown in Figure 4.1, were reviewed to correlate with the market needs analysis. These coal fields are geographically characterized in the following coal provinces: Appalachian, the Interior Provinces (Eastern and Western), and Western.

The potential coal resources are summarized in Table 4.1. As seen in this table, Identified and Hypothetical coal resources have been estimated to be several trillion tons. The Demonstrated Reserve Base (DRB) more narrowly estimates the coal resources to be nearly half a trillion tons (490 billion tons). Of this, over 80% of this coal resource estimate falls into three bodies: Appalachian bituminous (22%), Eastern Interior bituminous (22%), and western subbituminous (37%). The data in the DRB has been further categorized to separate that portion of the potential coal reserves which have 1.0% sulfur or less. That information is also shown in Table 4.1. These data show that over 80% of the low sulfur coal is in the western region (about 166 billion tons) with about 31 billion tons of low sulfur bituminous coal found in the Appalachian region.

A further categorization included is that of reserves recoverable by existing mining operations and by extension of existing operations. Thus, for those quantities it will not be required to open mining operations in new fields, establish new support and transportation infrastructure, and institute substantially more costly mining. By this restriction of reserves to current recoverability and existing mines, the reserve estimates are dramatically reduced to a total of 24 billion tons of which 8.2 are in the Appalachian region and 12.4 in the West. These are nevertheless substantial and sufficient reserve quantities.

Several general first-level conclusions regarding coal resources can be stated:

1. Because of sulfur emission regulations, the selected coals will be low sulfur coals, particularly low in organic sulfur since much of the pyritic sulfur can be removed by existing coal beneficiation methods. This will tend to favor using Southern Appalachian and Western coals. Since currently available coal preparation technologies are not expected to substantially reduce the organic sulfur content of high sulfur coals to acceptable levels, the organic sulfur content becomes almost an absolute and unmitigable criteria.
2. The low ash requirement will require use of the best available particle reduction and coal beneficiation technologies. Laboratory coal washability data can fairly represent the level of ash reduction that can be achieved. Since additional grinding can lead to further liberation of ash and mineral particles, as well as added process cost, there can be some flexibility in accepting coals based on ash criteria. Washability data can then be used as a guideline to selecting coals that can reasonably be reduced in ash to acceptable levels. This will be reviewed in Section 5.

Figure 4.1

Coal-Bearing Areas of the United States

Table 4.1

SUMMARY OF U.S. COAL RESOURCES
(Billions of Tons)

	<u>APPALACHIAN</u>	<u>INTERIOR PROVINCES</u>		<u>WESTERN</u>	<u>U.S.</u> <u>TOTAL</u>
		<u>EASTERN</u>	<u>WESTERN</u>		
<u>ESTIMATED IDENTIFIED AND HYPOTHETICAL</u>					
0 to 6000 feet	352	366	254	2995	3967
0 to 3000 feet	342	366	249	2622	3579
<u>IDENTIFIED RESOURCES</u>					
Bituminous	260	215	71	201	
Subbituminous	0	0	0	486	
Lignite	2	0	11	465	
Anthracite	<u>19</u>	<u>0</u>	<u>0.4</u>	<u>0</u>	
TOTAL	281	215	82	1152	1730

DEMONSTRATED RESERVE BASE

	<u>Und.</u>	<u>Surf.</u>	<u>Und.</u>	<u>Surf.</u>	<u>Und.</u>	<u>Surf.</u>	<u>Und.</u>	<u>Surf.</u>	
Bituminous	91	18	89	21	5	7	22	3	
Subbituminous	0	0	0	0	0	0	119	63	
Lignite	0	1	0	0	0	14	0	30	
Anthracite	<u>7</u>	<u>0</u>	<u>0</u>	<u>0</u>	<u>0</u>	<u>0</u>	<u>0</u>	<u>0</u>	
TOTAL	117		110		26		237		490

LOW-SULFUR PART OF DEMONSTRATED RESERVE BASE (1.0% S or less)

Underground	26.0	1.5	0.2	99.3	127
Surface	<u>5.2</u>	<u>0.2</u>	<u>0.8</u>	<u>67.0</u>	<u>73</u>
TOTAL	31.2	1.7	1.0	166.3	200
Low S as % of DRB	26.7%	1.5%	3.8%	70.2%	40.8%

RECOVERABLE RESERVES AT EXISTING MINES

Underground	6.6	1.7	0	1.0	9
Surface	1.6	0.5	1.2	11.4	<u>15</u>

3. Based on the relative size of coal resource estimates, candidate coals are most likely to be found in the Appalachian and Western regions. The Illinois Basin (Eastern Interior) has large coal reserves, but very little low sulfur coal, so is not likely to have suitable candidates for premium coal-based fuels. That is unfortunate because of the proximity of Illinois Basin coals to the markets.

4.2 Discussion of Market Assessment Approach

Task objectives in the Statement of Work specified that the coal-fuels be formulated from coals representing sufficient geographic diversity, abundance of supply reserves, economic mineability and quality characteristics to satisfy the market demand for these fuels. An estimate of the total potential annual demand of between 3 and 6 Quads (or roughly requiring 100 to 200 million tons per year of dry beneficiated coal) was provided on the basis of market analysis studies prepared separately by Eos and by Burns and Roe for PETC. Using that basis and information resource, the intention for this part of the task was the interpretation of market needs to provide guidance to the selection of candidate coals.

Using these DOE-sponsored, broad scale market assessments as a base, they were expanded into a more detailed analysis in order to provide a focused market input to the selection of coals for preparation as test fuels. The approach built upon two mechanisms: 1) a three-tiered market demand assessment approach, and 2) identification of a "representative CLM plant" for interpreting demand implications. The three tiers were comprised of the maximum coal use potential (MAXCUP), a focused reduced coal use potential (REDCUP), and an initial market entry coal use potential (MECUP). The "representative CLM plant" was based on materials balances and cost estimates in a previous study by EI and Combustion Engineering for PETC, and enabled interpretation of plant, capital and resource requirements to correspond to market sectors.

The study by Eos Technologies evaluated and estimated the potential applications of premium coal-based fuels in the residential sector. The studies by Burns and Roe similarly addressed the commercial and light industrial market sectors. The intent of those studies was to identify the maximum coal use potential (MAXCUP) for such advanced fuels and combustion applications. They further discussed some of the factors which will tend to constrain or limit the use of such fuels so that maximum potential is not likely to be ever reached. This study has used several assumptions to arrive at a reduced coal use potential (REDCUP) level that can usefully address the issues in coal selection that are the focus of attention here. Further discussion addresses the issue of market entry coal use potential (MECUP) to consider the earliest market entry coal selections.

The three-tiered market approach was developed from the broad-scale information base generated in the Eos and Burns and Roe studies. This provided an appropriate basis for the maximum potential coal use. In this study, all of these full use estimates were gathered together to formulate the MAXCUP assessment level. These estimates were based on a set of assumptions that are reviewed in Table 4.2.

Table 4.2

POTENTIAL MARKET FOR COAL-BASED FUELS
(No Environmental Constraints)

ALL AREAS

- Limited to households currently meeting primary space heating needs with premium fossil fuels.

NORTHEAST

- All households with over 5000 HDD/year.
- Exception: 50% of Pennsylvania households between 5000 and 6000 HDD/year.

MIDWEST

- All households over 6000 HDD per year.
- 33% of all households between 5000 and 6000 HDD/year.

SOUTH

- All households over 5000 HDD/year.
- 41% of households between 4500 and 5000 HDD/year.
- 15% of households between 4000 and 4500 HDD/year.

WEST

- All households over 6000 HDD/year.
- 33% of all households between 5000 and 6000 HDD/year.

*HDD = heating degree days

To more appropriately focus the market assessment, the maximum use estimates were reduced by assuming that environmental constraints would impose limitations on market acceptance and that limited penetration of the market would actually occur. It was assumed that environmental constraints would eliminate all urban, 50% of the urban-fringe residential and 75% of the urban-fringe commercial sector market opportunities. It was assumed that market penetration of coal fuels would be about 50% of the oil users and 10% of the natural gas users.

It was also important to identify the market segments where initial commercialization, or market entry, would be most likely. The application of advanced coal based fuels and combustion systems must be successful and represent an appropriate match of coal resource and market used in the initial commercial ventures or broader scale use will not ensue. The market and cost information to conduct a quantitative MECUP level of analysis is not available, so this was done qualitatively using subjective interpretation of the larger quantitative market assessment. The areas of greatest overall long-term market potential were viewed in light of the particular incentives needed for initial commercial ventures.

To aid in focusing and interpreting the market guidance to coal selection, it is appropriate to assess the market implications in terms of coal reserves and production levels needed, the number and distribution of fuel processing plants, and the practicality of developing the industry. For this purpose, it was decided to identify a "representative CLM plant" with typical production rates, costs, and reserve requirement. Information developed in a CLM plant cost estimate prepared by EI for Combustion Engineering under DOE Contract No. DE-AC22-82 PC50271 was used as a basis. Since the previous cost estimate included ash reduction to 2%, the deeper cleaning requirements for the current fuels selection was considered and adjustments to estimates were qualitatively made. The approximate descriptions of two types of representative plants are shown in Tables 4.3 and 4.4. The above referenced cost estimates were done for plants sized to be the minimum size economic plant. Since most of the plants in a broadly based market analysis would be larger sized, replicate plants, a representative plant producing at the 0.08 Quad level of production was also defined, that being about 2 1/2 times the minimum plant size.

After the market needs were determined by region and end use sector, the production requirements to satisfy the coal fuel quality requirements of various market segments were estimated. Using the estimating rates for the representative plants, the market implications and distribution of potential fuel plants were then identified.

4.3 Assessment of Market Needs

The purpose of market analysis in this task was to extract and interpret market based information to provide useful guidance and assistance in the selection of coals to be used for developmental testing. The approaches used for this assessment included a three-tiered market estimate and a CLM representative plant to enable interpretations of the market-based information, as was previously described.

Table 4.3

REPRESENTATIVE CLM PLANT

1. Defined in commercial case cost estimate study by EI for Combustion Engineering under DOE contract.
2. 183 tons/hr of clean coal product
 - at 16 hr/day = 2928 tons/day
 - at 330 days/year = 966,240 tons/year
 - at 14,300 Btu/lb = 30 trillion Btu/year
 - = 0.03 Quads
3. Capital investment required - coal cleaning and CLM
 - estimated in above study at \$40 to \$75 million for cleaning to higher ash level product
 - estimate: \$75 million
4. Coal reserves required
 - assume: 30 year plant life
 - 80% wt yield recovery
 - 60% mining recovery from reserve
 - reserve required = 2 billion tons/Quad
5. Above all for a minimum capacity economic plant, i.e., 0.03Quad standard replicate plant assumed at 0.08Quad

Table 4.4

ESTIMATING RATIOS FOR CLM PLANTS

	<u>Representative Plants</u>	
	<u>Minimum Economic</u>	<u>Standard Replicate</u>
Designation	ME	SR
Normal Size (Quads)	0.03	0.08
Clean Coal Product		
- tons/hr	183	500
- tons/yr	1 million	2.7 million
Capital Investment		
- millions \$	75	150
Coal Reserve Required		
- million of tons	60	160

The Eos and the Burns and Roe studies evaluated the maximum potential for application of these coal fuels. A summary of the MAXCUP level of estimates is presented in Table 4.5 for each of the use sectors and regions. This maximum estimate is dominated by the potential for coal use in the residential sector in the Northeast and Midwest regions, which comes to over 40% of the total estimated market of 7.4 Quads. This use level also represents nearly 20% of the current primary energy use of coal in the U.S. The 7.4 Quad estimate is about 10% of total primary energy use, so can be considered to be a major component of energy use. About half of the total 7.4 Quads are accounted for as residential (3.6 Quads) and nearly 75% (or 5.5 Quads) of the total in the Northeast and Midwest, including commercial and industrial estimates.

These market estimates at the MAXCUP level were translated using the representative plant estimating ratios from Table 4.4 to identify the market implications of the MAXCUP estimate. Table 4.6 reviews these implications. To supply the 7.4 Quad market, about 95 coal preparation and fuel processing plants would have to be constructed and brought into operation, with a capital investment required of about \$15 billion. To supply the needed 260 million tons per year of clean coal product, raw run-of-mine coal production of about 320 million tons per year would be required. This represents a 40% increase over current levels of U.S. coal production. If it were concentrated in the Appalachian coal production districts, this would be a 70% increase over current production levels. This would create a substantial impact on the coal mining industry as it expanded to such a large extent to meet the demand. The reserves of coal required to supply that market demand estimate would be about 15 billion tons, or half of the Appalachian low-sulfur portion of the DRB as indicated in Table 4.1.

The estimate of the needed 95 coal processing plants was based on the distribution of fuel plants as exhibited in Table 4.7 which reviews the plants required by use sector and region. It has been assumed that the coal products for both the residential and commercial sectors are the same, or at least sufficiently similar, so that they can be produced from the same coal resource and fuel plant. The industrial coal fuel product might have different fuel specifications and be produced in a different fuel plant. As expected from previous comments about the market demand distribution, the fuel plant distribution would be dominated by the 53 plants needed to supply the residential and commercial sectors in the Northeast and Midwest. At this MAXCUP level, a substantial number of the large scale commercial fuel plants would also be needed for other components of the MAXCUP estimated market, including 14 industrial sector plants in the South and 10 plants in the West. This would indicate that the MAXCUP demand level would require the use of a variety of coals from several different locations in each of the population regions as some geographic dispersion would be expected. The ability to support this MAXCUP level of premium coal fuel use in terms of the variety of coals, distribution of sources, infrastructure for transportation, construction, engineering, supplies, and capital and the reserves of reasonably available coal is not immediately evident.

Table 4.5

MAXIMUM COAL USE POTENTIAL

MAXCUP

(Quads)

	<u>Northeast</u>	<u>Midwest</u>	<u>South</u>	<u>West</u>	<u>Total</u>
Residential	1.5	1.6	0.2	0.4	3.6
Commercial	0.6	0.6	0.06	0.08	1.3
Industrial-Boilers	0.1	0.3	0.4	0.1	0.9
- Process Heaters	<u>0.3</u>	<u>0.5</u>	<u>0.7</u>	<u>0.2</u>	<u>1.6</u>
TOTALS	2.5 ===	3.0 ===	1.4 ===	0.8 ===	7.4 ===

Note: Above summarizes market estimates by
Eos and Burns and Roe.

Table 4.6

MARKET IMPLICATIONS

MAXCUP

Coal Conversion Market	7.4 Quads
No. of Plants	95
Capital Investment	\$15 billion
Clean Coal Product	260 million tpy
ROM Coal Required	320 million tpy - major production increases needed*
Coal Reserve Required	15 billion tons - half of Appalachian low S DRB

*40% increase over total U.S. current level
70% increase over current Appalachian total

Table 4.7

DISTRIBUTION OF FUEL PLANTS
MAXIMUM COAL USE POTENTIAL

MAXCUP

	<u>Northeast</u>		<u>Midwest</u>		<u>South</u>		<u>West</u>		<u>Total</u>	
	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>
Residential	1.5		1.6		0.2		0.4		=	3.6
Commercial	<u>0.6</u>		<u>0.6</u>		<u>0.06</u>		<u>0.08</u>		=	<u>1.3</u>
Plants for Residential/ Commercial		<u>26 SR</u>		<u>27 SR</u>		<u>3 SR</u>		<u>6 SR</u>	=	<u>62 SR</u>
Industrial										
- Boilers	0.1		0.3		0.4		0.1		=	0.9
- Process Heaters	<u>0.3</u>		<u>0.5</u>		<u>0.7</u>		<u>0.2</u>		=	<u>1.6</u>
Plants for Industrial		<u>5 SR</u>		<u>10 SR</u>		<u>14 SR</u>		<u>4 SR</u>	=	<u>33 SR</u>
GRAND TOTALS	<u>2.5</u>		<u>3.0</u>		<u>1.4</u>		<u>0.8</u>			<u>7.4</u>
Market (Quads) Plants		<u>31 SR</u>		<u>37 SR</u>		<u>17 SR</u>		<u>10 SR</u>	=	<u>95 SR</u>

- Notes:
1. A column is market size in Quads.
 2. B column is number of fuel process plants to supply market.
 3. All plants are Standard Replicate (SR) plants of nominal 0.08 Quad size.
 4. Residential and commercial markets can be supplied by product from the same plant.
 5. Industrial market may use a different product; higher ash and sulfur content may be acceptable in fuel.

Based on a variety of assumptions concerning the flexibility of energy supplies and the penetration of these new fuels into the identified market sectors, a reduced coal use potential (REDCUP) estimate was made and is presented in Table 4.8. These assumptions were discussed in Section 4.2 and are noted in summary at the bottom of Table 4.8 as reminders. By imposing the environmental constraint and partial market capture assumptions, the market demand at the MAXCUP level is reduced by factors of about 10 to 20 in arriving at the REDCUP estimate. The REDCUP total demand of over 0.5 Quads is only about 7.5% of the MAXCUP estimate. The REDCUP level is also dominated by residential demand in the Northeast and Midwest, some 58% of the total. As before, the implications of the REDCUP estimate on the market are shown in Tables 4.9 and 4.10, which includes the distribution of fuel plants required. This REDCUP estimate is a much more modest estimate of the premium fuels business than the MAXCUP estimate. An industry comprised of 5 large scale residential-commercial product fuels plants in the Northeast and Midwest and 4 minimum economic plants singularly distributed elsewhere can more reasonably be expected. The singular plants in the South and West might well have to distribute product very long distances because of the size of those regions. There may be a reasonable trade-off with the additional transportation costs of bringing in the product from a Midwest location. Thus, it may be possible to supply the REDCUP demand from a much more limited coal resource base.

As discussed in Section 4.2, identification of the specific market requirements for the initial market entry cannot be definitively made on the basis of the available studies and background information. Therefore, the market entry coal use potential (MECUP) is only reviewed qualitatively and probable market entry implications are only subjectively viewed. Since the MAXCUP and REDCUP levels are dominated by the residential-commercial sectors in the Northeast and Midwest, it is logical to assume that market entry would be initiated within that context. Market entry would likely occur where the best combination of low-cost coal fuel supply and high cost alternatives would exist. A number of such possibilities exist. Nevertheless, this market entry (MECUP) level of consideration suggests that market entry is as likely to be driven by technical performance and cost features of the coal fuel as by broadly based market size and distribution issues.

Table 4.8

REDUCED COAL USE POTENTIAL

REDCUP

(10¹² Btu)

	<u>Northeast</u>	<u>Midwest</u>	<u>South</u>	<u>West</u>	<u>Total</u>
Residential	210	117	20	25	372
Commercial	33	36	3	4	76
Industrial-Boilers	7	12	18	6	43
- Process Heaters	<u>12</u>	<u>21</u>	<u>31</u>	<u>11</u>	<u>75</u>
TOTALS	262 ===	186 ===	72 ==	46 ==	566 ===

Notes on Reduced Potential:

1. Environmental constraints reduce the market to non-urban and half urban fringe for residential and commercial
 - about 50% as shown in residential analysis (Eos)
 - assume 25% for commercial
2. Assume fuel preference market capture
 - 50% of distillate & residual fuel oil users
 - 10% of natural gas users

Table 4.9

MARKET IMPLICATIONS

REDCUP

Coal Conversion Market	0.75 Quads
No. of Plants	5 SR, 4 ME
Capital Investment	\$1.05 billion
Clean Coal Product	18 million tpy
ROM Coal Required	23 million tpy - 3% expansion of production
Coal Reserve Required	1 billion tons

Table 4.10

DISTRIBUTION OF FUEL PLANTS
REDUCED COAL USE POTENTIAL

REDCUP

	<u>Northeast</u>		<u>Midwest</u>		<u>South</u>		<u>West</u>		<u>Total</u>	
	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>	<u>A</u>	<u>B</u>
Residential	210		117		20		25		=	372
Commercial	<u>33</u>		<u>36</u>		<u>3</u>		<u>4</u>		=	76
Plants for Residential/ Commercial		<u>3 SR</u>		<u>2 SR</u>		<u>1 ME</u>		<u>1 ME</u>	=	<u>5 SR</u> <u>2 ME</u>
Industrial										
- Boilers	7		12		18		6		=	43
- Process Heaters	<u>12</u>		<u>21</u>		<u>31</u>		<u>11</u>		=	<u>75</u>
Plants for Industrial				<u>1 ME</u>		<u>1 ME</u>				<u>2 ME</u>
GRAND TOTALS	<u>262</u>		<u>186</u>		<u>72</u>		<u>46</u>			<u>566</u>
Market Plants		<u>3 SR</u>		<u>2 SR</u> <u>1 ME</u>		<u>2 ME</u>		<u>1 ME</u>	=	<u>5 SR &</u> <u>4 ME</u>

- Notes:
1. A column is market size in Quads.
 2. B column is number of fuel process plants to supply market.
 3. Standard Replicate (SR) plants are nominal size of 0.08 Quads.
 4. Minimum Economic (ME) plants are nominal size of 0.03 Quads.
 5. Residential and commercial markets can be supplied by product from the same plant.
 6. Industrial market may use a different product; higher ash and sulfur content may be acceptable in fuel.

5.0 COAL RESOURCE ANALYSIS

5.1 Background

With discussions of the U.S. coal resources and potential market needs as a background, the major thrust of the Analysis of Fuel Needs (Task 1) was to identify specific coals having the required characteristics and sufficient reserves for projected needs. Specific resource data listings for coal beds and characteristics were reviewed against selection criteria based on combustor requirements, emission constraints and market needs. A series of searches of coal data were conducted for the different requirements in order to recommend candidates for coals to be prepared as test fuels. The searches, criteria, and findings are discussed in the following sections.

5.2 Combustor Types

Those combustor types addressed by this program include: residential with heating capacity levels less than 100,000 Btu's per hour, commercial at 0.1 to 10 MM Btu's per hour and light industrial at 10-30 MM Btu's per hour. The unit classification of boilers and process heaters having firing rates of between 10-100 MM-Btu per hour have been assessed by Burns and Roe Services Corporation as being appropriate for retrofit application using coal based fuels. The relative sizing of the larger units, as compared to space heaters and small industrial process heaters, provides a cost effectiveness to include a post combustion particle removal system. This enables a wider range of feed coals to be utilized, expanding the potential reserve base of applicable coals in this classification. The two combustor designs, slagging and non-slagging proposed for the CBF program, each have unique fuel specifications, requiring specific coal qualities necessary for efficient operation and therefore, each combustor type will have a separate listing of applicable coal candidates.

5.3 Fuel Specifications

The fuel specifications for the smaller non-slagging type combustor for the residential, commercial and light industrial (RCLI) markets are shown on Table 5-1, and defined as ultimate and intermediate goals. These goals were developed by reviewing cost, environmental, and operational considerations to establish a generic approach to both CLM and dry micronized fuels production for a wide acceptance by both regulatory agencies and the proposed end user. Program selection of the more stringent ultimate goal level guarantees a broader regulatory acceptance. The ultimate goal parameters also provided a flexibility for sorbent additions necessary for utilization of a larger resource base with higher sulfur content feeds, while still adhering to the intermediate goal associated with a total percent feed ash. The DOE also preselected this set of criteria as input to the PRDA for the proposed combustion experimenters.

TABLE 5-1
EXPERIENCE GOALS FOR COAL-BASE RESIDENTIAL, COMMERCIAL AND INDUSTRIAL BOILERS APPLICABLE TO COAL SELECTION

A. FUEL	Residential Space Heat		Low Temperature Boiler		Medium Pressure Boiler	
	Ultimate Goal	Intermediate Goal	Ultimate Goal	Intermediate Goal	Ultimate Goal	Intermediate Goal
a) Ash Content, lbs/HRTU	<0.8	<1.5	<1	<2	<1	<2
b) Ash Properties						
- Ash Softening Temperature, of	>2500	>2500	>2500	>2500	>2500	>2500
- Slagging Index	-	-	<0.6	<0.6	<0.6	<0.6
- Fouling Index	-	-	<0.2	<0.2	<0.2	<0.2
c) Sulfur Content, lbs/HRTU	<0.5	<0.8	<0.5	<1.0	<0.5	<1.0
d) Coal Particle Size (process dependent)	-	-	-	-	-	-
e) Stability, months	>12	>6	>12	>6	>12	>6
f) Delivered Price, \$/HRTU (December 1985 dollars)	<\$5.00	<\$5.00	<\$5.00	<\$5.00	<\$5.00	<\$5.00
g) Density (HRTU/GAL)	>0.1	>0.11	-	-	-	-
B. AIRBORNE EMISSIONS						
a) Carbon Monoxide, lbs/HRTU	0.2	0.3	0.04	0.04	0.04	0.04
b) Volatile Organics, lbs/HRTU	0.03	0.5	0.01	0.02	0.01	0.02
c) Sulfur dioxide, lbs/HRTU	1.0	1.5	1.00	2.00	1.00	2.00
d) Nitrogen Oxides, lbs/HRTU	0.5	0.8	0.50	0.60	0.50	0.60
e) Particulate Matter, lbs/HRTU	0.1	0.4	0.05	0.10	0.05	0.10
f) Polycyclic Organic Matter lbs/HRTU	0.1	0.2	-	-	-	-

SOURCE: BSRC (May 1986) and EOS (December 1985)

For the larger combustors, amenable to a slagging type retrofit, the required fuel specifications differed significantly from the non-slagging combustors. Based on varying quantities of slag rejection, Figure 5-1 shows the potential increase in types of coal which were considered for the resource determination. Having a capability of high slag rejection affords an added benefit for potential removal for significant amounts of sulfur. Lime based chemicals (sorbent) introduced into the combustors have been shown to capture 30-50 percent of available sulfur in the coal feed, thus minimizing the release of SO₂ into the flue gases. Desulfurization technology in this form has exhibited this level of results using a stoichiometric ratio of 2:1 of lime to sulfur. At the 90 percent rejection level, these operating parameters calculate the maximum range of feed quality values from 0.5 % ash @ ≤1.8 % sulfur and up to 10 % ash @ ≤1.6 % sulfur.

For the slagging type of combustor, the ash chemistry becomes even more critical to the unit operation than the overall ash content. For this reason the ash softening temperature, which is a pre-determination to the T250 temperature, (i.e. slag flow temperature equivalent to a viscosity of 250 poise) was surveyed for coal selectivity. Ash fusion temperatures in the low (<2100 degrees F) to medium (2101 to 2400 degrees F range) categories coupled with a feed content meeting the particle and sulfur dioxide emission standards after slagging, assuming a 50% SO₂ reduction and 90% maximum ash rejection level, denotes the specific criteria used for resource evaluation and candidate selection for the classification.

5.4 Discussion of Selection Factors

5.4.1 Washability Characteristics

Coal cleaning technology utilizing surface and leaching chemistry concepts has advanced to stages of increased Btu recovery at finer sizes; however, much of the information is still proprietary and potentially process selective. These technologies are generally independent of washability characteristics. Based on the best information available on a broad survey of U.S. coals, the approach taken by this investigation was to apply the liberation potential found by analyzing washabilities of crushed products.

The Pittsburgh Energy Technology Center (PETC) database has been electronically compiled of nearly 1000 washability samples regionally collected from the major coal fields. An initial search was performed to determine the magnitude of analyses approaching the stringent specifications for commercial and light industrial process heating. Using a value of 2 percent ash for the 14 mesh by 0 size fraction and 1.30 float gravity, a list of 92 samples resulted. This list included bed samples from: Ohio, Pennsylvania, Maryland, Tennessee, Virginia, Alabama, Illinois, West Virginia, Kentucky (both eastern and western fields), Oklahoma, Iowa, Wyoming, Colorado, and Utah and essentially represented coal from all the major bituminous fields (see Appendix A, Table 1). Rejecting bed samples not conforming to the specified compliance sulfur emissions resulted in a 20 percent reduction in the number of original samples. These rejected coals were primarily from the states of Ohio, representing the Middle Kittanning, Lower Kittanning, Waynesburg and Brookville seams, from Pennsylvania repre-

Figure 5.1

ACCEPTABLE COAL ASH LEVELS FOR SLAGGING COMBUSTORS
(for Levels of Slag Rejection)

senting the Clarion seam, and from Western Kentucky and Illinois representing the Kentucky No. 6 and Illinois No. 6 seams, respectively. The remainder of the samples appear to exhibit deep cleaning potential applicability (i.e. greater than 40 percent yield values at the 1.5 percent dry ash level) required by the RCLI classification of the CBF program.

To determine the significance of a particular sample meeting the search criteria, a supplemental verification was performed to identify the number of samples representing each seam in the database. A calculated value (sample conformance %) used in Appendix 2.0 relates the percentage of total samples in the database for a specific coal bed that conforms to the stated specifications. The conformance number indicates the percent of those samples tested, (i.e. in the above cases generally 16-20 samples) that can be beneficiated to compliance sulfur level and less than 2 percent ash. Indications for improved qualities are implied by reviewing yield at ash levels.

Appendix A, Table 2 shows a revised list of coals meeting the commercial/light industrial specified feed characteristics of 1.5% ash @ 1.2 lbs SO₂ per MM-Btu's. These quality parameters reduce the potential reserve base to that only represented by the 30 samples. A map showing the geographical location of these samples is shown in Figure 5-2. Table 5-2 exhibits an abridged listing of coal beds for the commercial/light industrial classification using the preliminary screening results of resources to markets. Coals required for the residential market would be selected from the most cleanable of these coals. Even though the Lower Freeport, Upper, Middle, and Lower Kittanning beds did not consistently report ash levels $\leq$ 1.5 percent as indicated by the ultimate goal criteria, further investigation would be warranted.

Resource coals pertaining to the slagging type retrofit application were defined by using the low and medium ash fusion temperature criteria discussed in Section 5.3 as a first level matching criteria. Feed ash concentrations less than 8 percent are not critical especially when surveying the 1.30 low gravity cut point. For the two levels of ash fusion Appendix 2.0, Tables 3 and 4 were developed. As is apparent, the vast majority of these coals are represented by western subbituminous ranking.

5.4.2 Coal Quality Analysis

A search of the raw coal analysis included in the Pennsylvania State University database at the ultimate goal level identified only one sample (Kentucky C seam) meeting the RCLI fuel requirement. Even at the more relaxed specification of 2 percent ash (+/-) a 0.1 variance revealed only an additional two samples, one Kentucky C and one representing Upper Elkhorn #3 also from Kentucky. Based on bed correlations all three of these samples are representative of the same seam bed No. 151. This verifies the cleanability potential, even on a raw coal basis.

5.4.3 Supplemental Geological Survey Publications

Because of the identification of several samples from the Western Kentucky area and knowing the extensive reserve base of the Illinois basin, a data search of previously documented analysis from Illinois Geological Survey Publications was performed to seek similar sulfur quality levels of

Potential Low Ash Coals for Residential Application

Table 5.2

POTENTIAL FUEL CANDIDATES FOR COMMERCIAL/INDUSTRIAL APPLICATION (<1.5% ASH, COMPLIANCE)

SEAM	BED NO.	LOCATION*	ESTIMATED RESERVES (MILLIONS OF TONS)	*** YLD	AVG % CLEAN COAL ASH	AVG % CLEAN COAL SULFUR	AVG BTU/LB
Brookville	095	** PA, OH, MD	952.14	66.7	1.3	0.68	15030
No. 2 Gas	168	KY, TN, VA, WV	>2,500	69.3	1.2	0.76	14747
Black Creek	299	AL	71.52	83.0	1.0	0.62	15210
Hazard 5A	111	WV, VA, KY	>1,100	74.8	1.0	0.75	14519
Upper Elkhorn #3	151	WV, VA, TN, KY	>2,000	74.8	1.0	0.73	14594
Upper Elkhorn #2	154	KY, VA, WV	>1,200	73.6	1.3	0.79	14555
Upper Elkhorn #1	157	WV, VA, TN, KY	>1,000	73.2	1.2	0.67	14780
Chilton	135	WV, VA, TN, KY	>775	31.7	1.3	0.72	14998
Powelton	170	WV	206.32	53.3	1.3	0.69	15047
Coal Basin D	755	CO	83.13	65.2	1.5	0.60	14069
Coal Basin E	756	CO	83.64	80.9	1.3	0.33	14219

* Location refers to all states in which a particular seam has been identified.

** Underlined states reflect basis on which reserves and analyses are shown.

*** Average analysis only reflects composite results of samples meeting residential application criteria for level 5 cleaning (i.e.. 14X100M 1.30 float).

correlatable seams. A review of nearly 100 additional washability analyses performed with the same liberation size factor could not identify any which met the sulfur requirements. In all cases the organic sulfur portion was commonly in excess of compliance levels.

5.4.4 Availability/Coal Resource Data

For a Reduced Coal Use Potential (REDCUP) acceptance as defined by the market survey analysis, a minimum annual ROM coal production of 23 million tons would be anticipated for the coal based fuels program. The proportional distribution of markets shown on Table 4-8, requires that 65.7 percent of the total CBF production be directed toward the residential sector having the most stringent quality requirements. This mandates an abundant supply of premium grade CBF preferentially provided from several districts in the northern tier region where maximum utilization is expected, and establishes a necessary first order criteria for resource definition to markets.

The one billion tons of coal reserves required over a 30 year program period suggests approximately 10 coal beds, each having a 100 million ton reserve base. This quantity of reserve would help to guarantee a continuous, and qualitatively consistent supply of premium coals for maximum efficiency in the fuel selective boiler/space heater designs. Also, it is the intent of this survey to identify individual beds meeting the stated specifications rather than combining overlaying or nearby seams. This was important for two reasons: first, it provides a true definition of individual bed quality versus a blended quality of undefinable proportions and second, the vast majority of bed and reserve analysis was on an individual basis.

Recoverable reserves for the coal beds referenced in Section 5.4.1 and numerically identified (in columns 6 & 7) on Tables 1-4, Appendix A, have been quantified by county and state.

The reserve qualification of 100 million tons resulted in the elimination of several of the coal candidates listed in Appendix B, Table 2 for the residential/commercial/light industrial (RCLI) classification. Excluded from further consideration were several coals which could have provided regional diversity. Such coals are: the Black Creek seam from the Warrior Coal field in Alabama, Secor coal in Oklahoma which is also outside the Northern Tier region and the Coal Basin coals of Colorado. The exclusion logic has limited the remaining potential coal beds in this classification to be centrally located within Coal Producing Districts 7 and 8 of the Southern Appalachian field. Further discussion of geographic and transportation considerations as related to selection criteria logistics is presented in Section 5.4.6.

Slagging combustor coal selection criteria, based on reserve analysis was not as definitive; because, first the subbituminous coals have not been correlated, and second the majority of the coals identified did not include bed reserves but rather regional reserves combining several seams. It is commonly understood that vast amounts of recoverable reserves are available from these regions but without quantitative estimates of individual seams, bed quantifiability is uncertain. Selection of only those beds meeting the stated quality levels (i.e. <8 % ash, compliance and <=

2400 F ash soft temp) with conformance values ≥ 50 percent and with quantifiable reserves, resulted in the abbreviated list in Table 5.4, representing a regional diversity of coal candidates. Further review of available subbituminous suppliers with relationship to the consistent agreement of conforming values meeting the stated specifications implies an incomplete listing of the potential coal selection, especially for the subbituminous coals. For example, a review of "Coal Data 1986" shows two tables relating major coal production by both seam and mine. These tables identify several seams which were included in Appendix A, Tables 3 and 4, but failed to be included on the abbreviated listing because of insufficient information to confirm the adequacy of reserves. It is recognized that significant production records, regarding the western coal beds by recently started mines, implies sufficient future reserves. A supplementary list, identifying those select seams (meeting the slagging quality specifications) is provided on Table 5.3.

Table 5.3

<u>Seam Name</u>	<u>Bed No.</u>	<u>Producer</u>	<u>Mine I.D.</u>
Anderson	699	Amax Coal	Belle Ayr
Anderson	699	Triton Coal	Buckskin
Wyodak	699	Sunedco	Cordero
Dietz #3	697	Triton Coal	Buckskin
Deadman Upper/Lower	495/496	Bridger	Jim Bridger
Deadman Upper/Lower	495/496	Black Butte	Black Butte
Adaville	782	Pittsburgh & Midway	Kemmerer
Anderson & Dietz	927	Spring Creek	Spring Creek

5.4.5 Combustibility and Ash Slagging

This classification of selection criteria represents a number of second order selection variables which are combustor design related. The performance goals stated in Table 5-1 cannot apply directly to all fuels. For instance, in order to meet the 0.1 MM-Btu/gal density, criteria requires a selection of coals with bituminous coal ranking. In fact, a high volatile bituminous coal having a dry Btu content of 14500 at a 70 percent solids loading as required for CLM calculates to only 0.106 MM-Btu/gal and thus excludes all lower rank coals. This is inconsistent with the fuel specification survey discussed in Section 7.0, where several of the proposed combustion experimenters would prefer to use highly combustible high volatile subbituminous coal.

Combustibility is another second order variable. A method for determining combustibility which generally applies to all coals and which has been established in previous DOE sponsored work is the fuel ratio of fixed carbon to volatile matter. This selection criteria has been extensively used in the utility market to define suitable combustion characteristic coals and has been requested by the majority of the combustor experimenters.

Table 5.4

POTENTIAL COALS FOR SLAGGING TYPE COMBUSTORS

<u>DOE Sample No.</u>	<u>Coal Bed Name</u>	<u>Bed No.</u>	<u>Location Found</u>
	Ash Softening Temperature <u><2100°F</u>		
709	Dietz #3	697	WY
	Ash Softening Temperature <u>2101-2400°F</u>		
153	Lower Bakerstown	63	MD
188	Upper Freeport	71	PA
200	Upper Freeport	71	PA
403	Upper Banner	214	VA
406	Tiller	269	VA
545	Croweburg	496	OK
546	Croweburg	496	OK
618	H-Seam	154	CO
624	Upper Williamson	169	CO
625	Upper Williamson	169	CO
626	Upper Williamson	169	CO
710	Wyodak	699	WY
713	Wyodak	699	WY
737	Laramie No. 3	768	CO
847	Princess No. 7	77	KY (East)
860	Upper Elkhorn #3	151	KY (East)

 Note: Coals were identified by Sample No. in the
 DOE National Coal Database at PETC.

Based on the typical fuel specification, a fuel ratio of >2.2 is unacceptable. By definition, therefore, this eliminates all fuels with less than a 31.25% MAF volatile matter as shown on Table 5.5. In accordance to the "Standard Classification of Coals by Rank" adopted by ASTM, this criteria excludes all medium and low volatile bituminous coals in addition to all anthracites.

Application of this criteria to the preliminary suite of candidate coals for the RCLI classifications shows that only two coals displayed on Table 2 in Appendix 2.0 exhibit a higher unacceptable fuel ratio. These include the Lower Kittanning and Brookville seams. The remaining seams all meet this specification. The suite of coals at the higher 2% ash content essentially depict additional samples of the Northern Appalachian fields which do not meet the fuel ratio criteria including Clarion, Middle Kittanning, Upper Kittanning, Lower Freeport, Franklin, and Pittsburgh. It is to be noted that the preliminary selection of RCLI coals from districts 7 and 8 of the Southern Appalachian field, all meet the high volatile content criteria.

Application of this criteria to the slagging type combustor classification has shown that in the range of 4-8% ash on a moisture free basis, the fixed carbon cannot exceed 65.9-61.7 percent, respectively, or not less than 32.7-30.3 moisture free volatile matter. Of the 135 samples represented by two levels of ash fusion (Appendix A, Tables 3 & 4), only the Lower Kittanning in West Virginia did not meet this requirement.

Even more critical to the operation of the combustor than is ash fusion temperature are ash slagging and fouling characteristics. Ash slagging is the build-up of slag deposits on internal combustor surfaces. This can reduce the efficient transfer of heat, interfere with gas flow and potentially damage both furnace bottom and ash handling facilities when large masses build-up and fall. The predictive quality of this situation makes it a necessary second order fuel selection criteria.

This predictive index is determined by calculating the base/acid ratio (i.e., the ratio of $[\text{Fe}_2\text{O}_3 + \text{CaO} + \text{MgO} + \text{Na}_2\text{O} + \text{K}_2\text{O}]$ divided by $[\text{SiO}_2 + \text{TiO}_2 + \text{Al}_2\text{O}_3]$ from ash constituent analysis) multiplied by the percent sulfur in the coal feed. A value of <0.6 is acceptable relating to minimal slagging. Of the analysis reviewed, this index is generally between .33-.5 for the suite of RCLI candidate coals. The fouling or sintering index is determined by multiplying the base/acid ratio by the percentage of Na_2O . However, when only reviewing typical clean coals at a washing gravity of 1.60, a realistic analysis defining elemental ash constituents of the deep cleaned coals cannot truly be investigated without further testing.

Slagging coal selection does not suffer this same problem, because the desired product can normally be achieved at the higher gravity cut-points, however; in addition, the lower rank coals have inherently higher calcium and potassium deposits, therefore, the majority of these coals do not meet this requirement.

TABLE 5.5

COAL FUEL RATIO

ASSUME: 6% moisture for clean coal used in CWM Fuel. The chart is good for any per cent solids fuel.

% ASH		2		4		6		8		10	
MAF VM	VM	FC	FR	FC	FR	FC	FR	FC	FR	FC	FR
27.1	25	67	2.68	65	2.60	63	2.52	61	2.44	59	2.36
30.4	28	64	2.29	62	2.21	60	2.14	58	2.07	56	2.00
32.6	30	62	2.06	60	2.00	58	1.93	56	1.87	54	1.80
38.0	35	57	1.63	55	1.57	53	1.51	51	1.46	49	1.40
43.4	40	52	1.30	50	1.25	48	1.20	46	1.15	44	1.10
48.8	45	47	1.04	45	1.00	43	0.96	41	0.91	39	0.87

VM - Volatile Matter of CWM Coal

FC - Fixed Carbon of CWM Coal

FR - Fuel Ratio of CWM = $\frac{FC}{VM} \leq 2.2$

5.4.6 Transportation Considerations

The market discussion (Section 4.0) identified the regional markets for CBF to include primarily the northeastern tier of the Appalachian coal fields and a portion of the northwestern tier of the United States, including the states of Colorado, Wyoming, North Dakota, South Dakota. With regard to the selection of a suite of candidate coals, all regional areas of the U.S. were surveyed including those regions discussed. As implied in Section 5.4.4 insufficient comparative and quantitative data pertains to the Western coals, therefore, the following was developed in an attempt to ascertain the final fuel cost impact of shipping coals, for the RCLI application, exclusively from Districts 7 and 8 of Southern West Virginia and Eastern Kentucky to the western regions of the U.S. By using transportation as the cost justification variable, a comparison was made of the calculated projected fuel prices to the fuel cost criteria (shown on Table 5.1) of less than \$4.50 and \$5.00 per gallon for the commercial/light industrial and residential markets, respectively. The primary mode of transportation from the Eastern Kentucky region would be by rail. The complex structure of rail system pricing makes it difficult to project specific rail costs. Literature search discovered an approximation guideline described in the 1978 edition of "Coal Preparation for Combustion and Conversion." The described methodology utilizes a system of exponential rate formulas for both long and short hauls. Understanding that the mileage rates used in their formulas are not currently accurate, they were still used for comparative regional cost differentials.

Current freight charges and relative coal pricing were evaluated using the price indicators annually reported by the U.S. DOE/EIA. This data (graphically shown on Figure 5-3) relates the general increase trend in freight charges since 1978, which was used for justifying current transportation costs. As shown, freight charges have increased approximately 168 percent over the past 6 years.

According to the experimental rate formulas, for a long haul at 1250 miles (i.e., approximate distance from Eastern Kentucky to the Rocky Mountain Region) would cost 7.08 mils per ton-mile or \$8.85 per ton. With a 168 percent trend factor, this increases to \$14.87 per ton cost. For comparison purposes, a supplemental exercise was performed, identifying similar distance hauls from the Northwest Region, (Table 5-6) amounting to between \$35-\$40 per ton or approximately 425 percent price increase.

With reference to the projected costs of a minimum economic plant discussed in Section 4, annual cost data for the three previously selected coals calculated to between 72 and 123 dollars per ton produced. To be conservative, combining the average of larger transportation costs, results in a per ton cost of \$109.5 to \$160.5, and assuming a 14500 Btu/lb cleaned product results in a cost per million Btu's of \$3.78 - \$5.5 dollars. This value, which exceeds the fuel cost criteria not including local transportation or profit margins, suggests the need to provide a RCLI coal from the Rocky Mountain Region. Even using the lower transportation cost results in a marginally acceptable \$3.00 to \$4.75 per MM-Btu's FOB slurry plant.

FIGURE 5.3

Data Source: Freight charges and price ratios were determined from information reported by the U.S. DOE/EIA - 1986 Coal Data published by the National Coal Association.

Table 5.6
CURRENT FREIGHT CHARGES

<u>Origin</u>	<u>Destination</u>	<u>\$/Ton</u>
Colstrip, Montana	Hibbing, MN	23.07
Colstrip, Montana	Brooken, MN	21.87
Kuehn, Montana	Ashland, WI	25.02
Colstrip, Montana	Minneapolis, MN	25.55
Kleanburn, Wyoming	Seattle, WA	38.16
Sheridan, Wyoming	Spokane, WA	30.92
Gillette, Wyoming	Tupelo, MS	42.22

Source: Coal Week 1984 (Burlington Northern Shipper)

Survey of the database for Rocky Mountain regional coals meeting the quality specifications, <1.5% ash, revealed only the bituminous coals from the Coal Basin D and E seams in Colorado. These coals were originally eliminated on the basis of insufficient reserves; however, because of the reduced regional fuel demand (Table 4.8) being only 8 percent of the total market, indicates that a coal selection associated with smaller reserves could be justified. Eight percent of the 1 billion ton required reserve base calculates to 80 million tons. These selected coal beds located in the Somerset field of the Uinta Region each contain approximately 83 million tons reserve, which is adequate for the regional market requirement.

5.4.7 Slurryability of CLM

The preceding has established the generic criteria for a suite of coals satisfying the coal based fuels program. This general criteria did not take into account the form of fuel which is to be prepared from the two forms of fuel proposed for this program, nor does it take into account the intrinsic characteristics of either a coal liquid based fuel with reference to stability of the fuel or the flowability of dry dense powder. The following sections will attempt to define those necessary components of a user satisfied fuel and the application of those components to more specific selection criteria.

A number of factors come into play in deriving a stable slurry such as inclusion of the transport medium be it oil, alcohol or water, the size distribution of the coal particles, and the chemical dispersant. Of these three variables, based on publically available data, the transport medium and dispersant are not directly related to coal selection. The size or particle distribution appears to be a more regulative factor. It has been shown through a number of studies that this factor is primarily responsible for the maximum solids loading which can be achieved in a coal liquid mixture while achieving a flowable minimum viscosity. The optimum particle size can be achieved by a number of means, first multiple stage grinding so that a blend of grinds will produce the desired end product or second, the selection of a coal with a grindability which will ultimately produce the desired distribution through a single stage of grinding. The latter will result in more economical processing. It has been shown that grinding a coal with a high Hardgrove Grindability Index (HGI) will produce a more uniform or more widely dispersed distribution, aiding in natural coal stability.

The HGI for the entire suite of RCLI candidate coals lies between 38-53 with the Eastern "Elkhorn type" between 38-45. This implies that a blend of grinds may be required for optimum particle size distribution. The slagging coal selection shows HGI values generally in the same range.

5.4.8 Flowability of Dry Dense Powder

Preparation of dry dense powder fuel is based on pulverizing or "grinding" the premium grade fuel to ultrafine micronized sizes. Ultrafine being defined at 100 percent minus 400 mesh. Wet micronizing is the easiest to accomplish, but thermal or flash drying would be required to produce an acceptable dry dense powder fuel, nominally in the range of less than 1 percent surface moisture. The second method of preferred grinding, is "dry"

using either compressed air or steam as the transport medium. This technology provides finely disseminated particles from the product stream.

The grinding aspect and particle size distribution is as important to the final product as is coal liquid mixtures. The resultant product must be flowable without having the tendency for hardpacking during settling, transportation or storage. Consideration of these fuel characteristics is necessary when selecting candidate fuels. However, minimal research effort has been performed to determine the optimal size distribution for maximum flowability, resulting with an undefinable selection criteria. The main emphasis, as with the coal liquid mixtures, is dependent on the grindability characteristics of the coal, for producing the desired product distribution with disseminated particles without unnecessary blends of grinding streams, and in inherent moisture level amenable to the grinding process for the production of a low final moisture product. Because minimum effort has been expended in the area of micronized coal flowability, the method proposed for determining optimum flowability of the prepared fuels will be the ASTM standards D 1895 8.02 for pourability used in a number of industries including paint, pigment and plastics. This will serve to provide a guide for future coal selection.

5.5 Selection of Candidate Coals

5.5.1 Selection Criteria

The market requirements and the recommended fuel specifications to meet the PETC performance goals for the advanced fuels and combustion development program were reviewed. In addition, the data available to the coal resource and evaluation process were also reviewed. Based on these considerations, criteria were selected for the review and recommendation of candidate coals. It was decided to compare cleaned coal properties in the PETC coal washability database against these selection criteria. Thus, it was necessary to choose criteria that are consistent with the available information. For example, consideration of ash chemistry would have been useful in the selection because of effects on combustion properties. However, the database does not consistently provide ash chemistry for the washed coal product fractions, so such criteria could not be used.

The criteria chosen for the selection of candidate coals are shown in Table 5.7.

Table 5.7

CANDIDATE COAL SELECTION CRITERIA

	<u>RCLI Fuel*</u>	<u>Slagging Fuel</u>
Ash Content (%)	<1.5%	<8%
SO ₂ Emissions (lbs/MM Btu)	<1.2	<1.2
Sample Conformance**	>50%	>50%
Coal Bed Reserves (millions of tons)		
First Round Selection	>100	>100
Additional Selection	>80	N/A
Ash Softening Temperature (°F)	N/A	<2400

*Residential, commercial, light industrial fuels

**Percent of samples in database for the specific coal bed
that conform to stated specifications.

It was decided to use these selection criteria with the following notations:

1. For the RCLI fuels, the ash content level of 1.5% when combined with the higher values of heat content that are typical of deeply cleaned coal fractions will for most coals readily meet the "intermediate goals" of 1.5 lb/MM Btu for the residential and 2.0 lbs/MM Btu for the commercial and light industrial applications and the "ultimate goal" of 1.0 lb/MM Btu for the commercial and light industrial category. Meeting the residential "ultimate goal" of 0.8 will be more difficult.
2. The ash content level for slagging fuels was based on calculations and assumptions regarding ash rejection in slagging combustors.
3. The criteria for sulfur content and emissions represent the "new source performance standard" (normally applicable to large boilers) of 1.2 lb SO₂/MM Btu for slagging combustors and for RCLI fuels.
4. Primary candidate selections were required to have bed reserves of at least 100 million tons in the initial screening.
5. Secondary candidate selections which would serve certain specific and limited markets segments were made on the basis of reduced reserve requirements (80 million tons).

5.5.2 Resource Evaluation and
Recommendation Procedures

Available data were screened by comparison against selection criteria in order to eliminate from consideration those coals which do not come close to satisfying criteria and focus on those that might meet the

desired characteristics. The electronically compiled database at PETC of nearly 1,000 washability samples was chosen as the primary data source. Additional information, such as that contained in the Keystone Coal Industry Manual, Penn State database, geological survey data from state publications and the Keystone seam production data was selectively used as needed.

Two initial database screenings were made to provide lists of potential candidates for RCLI fuels using the 14 mesh by 100 mesh size fraction and 1.30 specific gravity float data from the washability sample database. A screening of samples with less than 2% ash was made to determine the magnitude of the number of samples that approach the stringent criteria; 92 samples were listed. Following the initial screening, a more focused set of sequential screenings against the RCLI criteria in Table 5.7 produced: (a) a listing of 30 candidates that met the 1.5% ash level, then (b) a reduced list of 11 candidates obtained by applying additional criteria. The final screening list of 11 was derived by: combining beds with common bed correlation numbers; eliminating samples for which the 1.5% ash did not correspond to the 1.0 lbs/mm Btu goal (i.e., heat content yield too low); not including beds with insufficient reserves; and applying the remaining criteria, such as sulfur emissions, yield and sample conformance. From that list of 11, a group of five candidate coals were recommended for the coal supply phase of the program. Those recommendations were made by comparison of the candidate list of 11 against the market assessment, transportation requirements, and projected availability of reserves.

It should be especially noted that at no time were the coal database sample information entries interpreted in an absolute sense. It was recognized that coal samples may or may not be representative of the resource and that there are wide margins of variation in the data. Thus, the screenings were conducted with ample use of judgement in order to perceive general observations about which coals would likely be recommended for further consideration.

A screening of candidates for coal fuels for slagging combustors using the criteria of Table 5.7 produced a list of 15 coal beds which meet both quality and reserve specifications. Candidate recommendations have not as yet been made, pending the provision of more specific requirements for slagging combustor development.

The procedures for selecting candidate coals as described above were followed in an orderly and methodical manner. However, it was appropriate to supplement the procedure with subjective, professional judgments which derive from an understanding of the information being used to select coals. There are substantive variations in the reported properties of coal samples for both raw coal and washed coal fractions, so ultimately the coal-based premium fuels (both slurry and dry ultrafine) will need to be tailored based on specific source coals and anticipated uses.

Without demonstrated, economically viable cleaning and fuel preparation processes selected, it was impossible to use a candidate coal recommendation procedure that was either process specific or that would enable rating against an absolute scale. Since the intent was to enable the recommendation of suitable candidates to supply representative premium fuels, the inability to select a "best" coal in light of available information was not of particular concern. While it is anticipated that the

reported clean coal properties from laboratory washability studies (such as sulfur, ash, yield, etc.) may not in all cases be attained in the larger scale processing to supply the required quantities for combustion testing, this information has provided the most reasonable basis for selections. The actual qualities of the fuels supplied will yet be demonstrated in the characterization and processing tasks of the program.

5.6 Resource Evaluation Conclusions

Given a defined set of stringent fuel characteristics, two suites of candidate coals have been selected, one to satisfy the advanced combustor needs for the RCLI market and the second for the slagging type combustor market.

5.6.1 RCLI Fuels

- From a database of nearly 1000 samples representing over 200 coal beds, a select few coal seams have been identified which can be "Semi" conventionally beneficiated for the production of 1.5 percent dry ash at compliance levels. These fuel characteristics allow coal-based fuels to be competitive with natural gas and oil. Residential market candidates will be selected from the most cleanable of these.
- The resources associated with the select coal beds identified are proportionately distributed to the regional market areas. The suite of candidate coals is within a 700 mile radius to all market areas.
- For the one billion tons of reserve required for coal-based fuel production, an excess of 14 billion tons have been correlated to the select coal beds.
- The coals identified, with the exception of Coal Basin D and E coals of Colorado, have been previously used by several slurry manufacturers and proven slurryable.
- Ash slagging and fouling characteristics of the select coals appear to be within specifications at conventional cleaning plant specific gravities, however, the effect of "deep" cleaning on ash characterization will need to be further investigated.
- Slurry stability and dry dense power flowability depend on grinding characteristics of the selected fuels. These factors will have to be further evaluated by slurry manufacturers and the effect of the Hardgrove Grindability Index considered with regard to specific fuel processing.
- Additional coal beds, either not included in the database or which could be beneficiated with advanced cleaning technology, could significantly expand the regional diversity of the resource base. For the near term projected use of coal-based fuels, the identified suite of candidate coals will satisfy all demands. A large number of coal producers have been identified mining these select coals.

5.6.2 Slagging Combustor Fuels

- Use of slagging type combustors can decrease the strict requirement of feed ash and sulfur content for potential resource expansion, but places a second demand, namely, ash softening and T250 temperatures, on the selection of fuel candidates.
- A list of 13 coal beds have been identified meeting both quality and reserve specifications. The coals are regionally located to supply the required demand for all market sectors in this classification.
- Even with the expanded quality specifications no coal seams from the Midwest Region, including the Illinois Basin, have been identified with reliable confidence conformity.

6.0 CANDIDATE COALS

The recommended candidate coals for the stringent fuels requirements for the residential, commercial, and light industrial market segments (RCLI) fuels) are presented in Table 6.1. From these recommended candidates, it is anticipated that a coal fuel source of representative qualities will be identified and characterized as the baseline RCLI fuel. In addition, an option for supplying the Western, Northern Great Plains, and Rocky Mountain regions has been provided by including the Colorado coal, even with lesser reserves identified. Recommendation of additional candidates to supplement the baseline fuel supply can be made if appropriate, using the information collected in this task.

The most current listing of candidate coals for slagging combustors is presented in Table 6.2. A final screening and evaluation is yet needed to present recommended coals for slagging combustors.

The ability to select coals for these requirements depends, in great extent on the availability and quality of information resources about specific coal resources. The PETC coal database is the most extensive and complete compilation of coal resource information. However, there are some apparent incongruities in the information in the database, and in some instances, information that would aid the selection is not available in the database. Thus, the selection process is only as good as the information resource and is not perfect. In the long run, the delivered fuels, having been carefully characterized and processed, must meet the fuel specifications. The coal selection process provides some assurance that fuel specifications will be attainable and that the fuels used in testing will be representative of the future advanced premium-quality coal-based fuels and available in sufficient reserve and proximity to meet anticipated market needs.

These lists of candidate coals for RCLI and slagging combustors were generated principally by the stated selection procedures, using the selection criteria for selective search and elimination steps, and supplemented by judgement. The database is comprised of information gathered in sampling and laboratory testing programs over a period of many years. In addition, coal properties are known to vary significantly over relatively short distances, such as from top to bottom of seam or even a few feet along a seam. Therefore, it may be quite difficult to use this database and selection process to locate specific coals for purchase and supply purposes. Such was not the intent of PETC in developing this database, nor of EI in conducting this task. Rather, it was important to use the procedure and data to identify patterns or trends such that candidate coals can then represent most likely opportunities to meet the performance goals.

To the extent that was possible, bed correlations were used to help identify the total reserves available across state, county, or district lines. Such bed correlations are helpful because coals are often known by different names at different locations, making it sometimes difficult to relate information from one data set to another. Unfortunately: (1) bed correlation numbers are not consistently or extensively used with all data, (2) much of the information is not reported in a correlated manner, (3) mine operators and coal suppliers are not particularly concerned about the seam

Table 6.1

CANDIDATE COALS FOR RESIDENTIAL,
COMMERCIAL, AND LIGHT INDUSTRIAL MARKETS

<u>Bed Number</u>	<u>Coal Bed Name</u>	<u>Related Names</u>	<u>Locations Found</u>	<u>Original Estimated Reserves (tons)</u>
151	Upper Elkhorn #3	Cedar Grove, Jellico, Taggart	WV,VA,KY,TN	12,558,191,000
154	Upper Elkhorn #2	Lower Cedar Grove	WV,VA,KY	3,525,101,400
157	Upper Elkhorn #1	Alma, Blue Gem	WV,VA,KY,TN	9,402,073,300
168	Lower Elkhorn	No. 2 Gas, Pond Creek	WV,VA,KY,TN	11,015,747,000
755	Coal Basin D	Oliver	CO	83,000,000

Table 6.2

CANDIDATE COALS FOR SLAGGING COMBUSTORS

<u>Rank</u>	<u>Bed No.</u>	<u>Coal Bed Name</u>	<u>Related Names</u>	<u>Locations Found</u>	<u>Original Estimated Reserves (10³ tons)</u>
B	63	Lower Bakerstown	Thomas Three Foot	MD,PA,WV	539,550
B	71	Upper Freeport	Big Vein	MD,OH,WV, PA,KY	8,555,660
B	77	Princess No. 7	Coalton	KY	138,020
B	151	Upper Elkhorn #3	(See above)	WV,VA,KY,TN	12,558,191
S	154	H-Seam		CO	252,520
S	169	Upper Williams		CO	183,080
B	214	Upper Banner		KY,VA	255,920
B	269	Tiller	Lower Iaeger	WV,VA	166,180
B	495/ 496	Deadman (Upper/Lower)			189,500
S	496	Croweburg	Fireclay No. 2	KN,OK,MO	578,640
S	697	Dietz #3	Canyon	WY,MT	2,537,700
S	699	Anderson- Wyodak		MT,WY	18,372,800
S	768	Laramie No. 3		CO	302,410
S	782	Adaville		WY	932,200
S	927	Anderson/Dietz		MT,WY	3,858,290

Rank: S = subbituminous, B = bituminous

name, related names or bed correlations, and (4) western seams are generally not correlated.

Some of the consequences of the above information and bed correlation considerations are as follows:

1. A few samples of Northern Appalachian and Illinois Basin coals were identified as having properties close to or satisfying the criteria. Apparently being individual samples, few in number (low in conformance), it was assumed that they are non-representative of resource quantities sufficient to meet the market needs. There was no reasonable, logical or defensible basis in the data to support a recommendation of one of these as a candidate coal even though it would be highly desirable to have a candidate coal such as these in close proximity to markets. The data and correlations are insufficient to justify this.
2. Very few of the coals listed in the tables will satisfy the performance goals for sulfur emissions while being at least close in meeting the other criteria -- as based on the conventional washability data. It was decided to use the new source performance standard of 1.2 lbs SO₂/MM Btu instead to broaden the base of candidates at this slightly higher limit. This was done with the expectation that actual coals purchased, cleaned and supplied will contain lesser amounts of sulfur.
3. The use of bed correlations to include related seam names where appropriate in the Southern Appalachian coal fields enable the aggregation of larger supporting reserve quantities.
4. The final recommendation of candidate coals with identifying and related bed names was strongly influenced by the bed correlations. Thus, for example, the Lower Elkhorn bed was a recommended candidate even though the Lower Elkhorn label doesn't appear on samples passing the criteria. Samples from several related beds do pass and the Lower Elkhorn reserves are high. The lack of sample experience was not a sufficient basis to eliminate what appeared otherwise to be a strong candidate.
5. Because some of the Western coals and even some of the Southern Appalachian coals can commonly satisfy combustion performance standards without washing, the washability database is not as extensive for these coals. Also, Western coals are not strongly correlated, presumably because the need to do so has not been strong and the geology can be complex. Therefore, evaluating Western coals was constrained by a dearth of information. The reserve criteria was modified to permit the recommendation of a Western candidate coal, because:
 - It was important for geographic diversity and market proximity to have a Western coal candidate,
 - With few exceptions, the Western coals are substantially lower in sulfur content and consistently so,

- Western resources are generally believed to extend in quantity well beyond the immediately identified reserve and so are likely to be plentiful for market needs, even though correlation information is not available to support this contention,

It is important to note the evident patterns in the selection process. The final list of recommended candidates for the RCLI fuels is dominated by Southern Appalachian low-sulfur coals (from Eastern Kentucky, West Virginia and Virginia), all from Producing Districts 7 and 8. Numerous other samples from the same area were also among the list of late eliminations. Thus, it is concluded that (1) the potential choices are dominantly from those resources, (2) there are many options to supply suitable coals, (3) specific selections are dependent on the quality and cleaning characteristics of the currently available mined portions of the resource or seam, and (4) the selected candidates are representative of the extensive resource that will be available for this market application.

7.0 FUEL SPECIFICATIONS & SUPPLY

In order to establish the types and quantities of fuels necessary to carry out the Department of Energy's Advanced Combustor Program, a fuel specification and supply survey was sent to each of the combustor contractors. Based on their replies to this survey, along with the specifications detailed in the original PRDA, a set of specifications for each of the fuel types was established. These specifications are given in Tables 7.1 and 7.2. While there may be some variances for an individual contractor, these specifications are consensus requirements and will cover 90% of the fuel requirements for this program.

It can be seen that there are slightly different specifications for the fuel depending upon whether it is a solid or slurry fuel and whether it is for the residential, commercial or light industrial market. Not surprising, however, is the necessity for all fuels to be low in ash (except for the slagging combustors) and low in sulfur to meet current and anticipated emission standards. These emissions requirements (0.8 lbs/mm Btu for ash and 0.5 lbs/mm Btu for sulfur) then dictated that the coal selection process be based upon cleanability criteria as well as the reserve base and the proximity to markets.

The fuel specifications defined by the combustors also indicated the necessity for a high ash fusion temperature (again, except for the slagging combustors) to prevent fouling and slagging in the combustion chamber. This value is generally greater than 2200°F and must be the value for the clean, rather than the parent, coal. This then became another criteria for the coal selection process.

The fuel requirements as determined from the survey and conversations with the combustor contractors indicates that, over the life of the contract, a total of 100 to 200 tons of solid coal and from 75 to 100 thousand gallons of coal-water slurry may be required. The exact amount will depend upon the success the contractors attain as they move through the various development stages.

Table 7.1
Specifications For Solid Fuel

Fuel Type	Coal Rank	Particle Size (mean)	Max Topsize um	% Volatile Matter	% Ash	% Sulfur	BTU Content	Ash Soft. Temp., deg F
Residential	bituminous	10	40	30-55	<1	<1	13,500	>2700
Commercial	bituminous	10	40	30-55	<1	<1	13,500	>2200
Lt. Industrial	bituminous	40	150	30-55	<6	<1	13,500	>2200

Table 7.2
Specifications for Coal Water Fuels

Fuel Type	Coal Rank	% Volatile Matter	% Ash	% Sulfur	BTU Content	Ash Soft. Temp., deg. F	Particle Size (mean)	Max Topsize um	% Solids	Viscosity cps
Residential	bituminous	30-55	<1	<1	10,000	>2600	10	40	65-70	<1000 @110/sec 70 deg F
Commercial	bituminous	30-55	<1	<1	10,000	>2600	40	150	65-70	<1000 @110/sec 70 deg F
Lt. Industrial	bituminous	30-55	~6	<1	10,000	>2600	40	150	65-70	<1000 @110/sec 70 deg F

APPENDIX A

Appendix

CANDIDATE COAL LISTINGS

	<u>Pages</u>
Description of Information in Columns of Tables 1 & 2	A-1
Description of Information in Columns of Tables 3 & 4	A-2
Table 1 -- 1.30 Float Product Less than 2.0% Ash	A-3 to A-8
Table 2 -- 1.30 Float Product Less than 1.5% Ash	A-9 to A-11
Table 3 -- Less than 2100°F Ash Softening Temperature	A-12 to A-14
Table 4 -- 2101 to 2400°F Ash Softening Temperature	A-15 to A-23

Note: This tabulated data was obtained in December of 1986 from the National Coal Technology Database located at the Pittsburgh Energy Technology Center. Information in this Appendix is explained on pages A-1 and A-2.

<u>COLUMN NO.</u>	<u>DESCRIPTION OF INFORMATION IN COLUMNS - TABLES 1 & 2</u>
1	Sample number in DOE database
2	-----
3	County name where sample taken
4	State name where sample taken
5	Local name of coal bed where sample taken
6	DOE bed correlation number
7	Estimated coal reserves for the designated coal bed in county reported (millions of tons)
8	Estimated coal reserves for the designated coal bed in state reported (millions of tons)
9	Sample conformance percentage (%) -- The percentage of total samples in the database for a specific coal bed that conforms to the stated specifications. For example, the percent of 1.30 float product samples for the 14Mxl00M size fraction that were cleaned to compliance sulfur level and ash level less than 2% (Table 1) or 1.6% (Table 2).
10-15	<u>Reported data for cumulative float product at 1.30 specific gravity on 14Mxl00M coal size fraction in standard washability</u>
10	Cumulative weight percent yield of product at stated sp.gr.
11	Percent ash content
12	Percent total sulfur content
13	Percent pyritic sulfur content
14	Heat content (Btu/lb)
15	Calculated sulfur emissions with no sulfur reduction (lbs of SO ₂ /MMBtu)
16-20	<u>Reported data for cumulative float product at 1.40 specific gravity on 14Mxl00M coal size fraction in standard washability</u>
16	Cumulative weight percent yield of product at stated sp.gr.
17	Percent ash content
18	Percent total sulfur content
19	Heat content (Btu/lb)
20	Calculated sulfur emissions with no sulfur reduction (lbs of SO ₂ /MMBtu)
21-25	<u>Reported data for cumulative float product at 1.30 specific gravity on 3/8"xl00M coal size fraction in standard washability</u>
21	Cumulative weight percent yield of product at stated sp.gr.
22	Percent ash content
23	Percent total sulfur content
24	Heat content (Btu/lb)
25	Calculated sulfur emissions with no sulfur reduction (lbs of SO ₂ /MMBtu)
26-32	<u>Reported data for 1.60 specific gravity float clean coal</u>
26	Percent fixed carbon (moisture and ash free basis)
27	Coal fuel ratio = % Fixed Carbon / % Volatile Matter
28	Hardgrove Grindability Index
29	Free Swelling Index
30	Ash Fusion Temperature (Reducing) - Softening (F)
31	Ash Fusion Temperature (Reducing) - Deformation (F)
32	Ash Fusion Temperature (Reducing) - Fluid (F)

<u>COLUMN NO.</u>	<u>DESCRIPTION OF INFORMATION IN COLUMNS - TABLES 3 & 4</u>
1	Sample number in DOE database
2	Database cross reference number
3	County name where sample taken
4	State name where sample taken
5	Local name of coal bed where sample taken
6	DOE bed correlation number
7	Estimated coal reserves for the designated coal bed in county reported (millions of tons)
8	Estimated coal reserves for the designated coal bed in state reported (millions of tons)
8A	Sample conformance percentage (%) -- The percentage of total samples in the database for a specific coal bed that conforms to the stated specifications For example, the percent of 1.60 clean float product samples with ash softening temperature less than 2100 F (Table 3)
9-14	<u>Reported data for cumulative float product at 1.30 specific gravity on 14Mx100M coal size fraction in standard washability</u>
9	Cumulative weight percent yield of product at stated sp.gr.
10	Percent ash content
11	Percent total sulfur content
12	Percent pyritic sulfur content
13	Heat content (Btu/lb)
14	Calculated sulfur emissions with 50% sulfur reduction by slagging (lbs of SO ₂ /MMBtu)
15-19	<u>Reported data for cumulative float product at 1.40 specific gravity on 14Mx100M coal size fraction in standard washability</u>
15	Cumulative weight percent yield of product at stated sp.gr.
16	Percent ash content
17	Percent total sulfur content
18	Heat content (Btu/lb)
19	Calculated sulfur emissions with 50% sulfur reduction by slagging (lbs of SO ₂ /MMBtu)
20-32	<u>Reported data for 1.60 specific gravity float clean coal</u>
20	Cumulative weight percent yield of product at stated sp.gr.
21	Percent ash content
22	Percent total sulfur content
23	Heat content (Btu/lb)
24	Calculated sulfur emissions with 50% sulfur reduction by slagging (lbs of SO ₂ /MMBtu)
27	Hardgrove Grindability Index
29	Ash Fusion Temperature (Reducing) - Softening (F)
32	Percent volatile matter (moisture free basis)

TABLE 1
Less than 2.0% Ash

A-3

DOE				COALBED	BED	ESTIMATED RESERVES		1.30 FLOAT 14M X 100M		TOTAL	PYRITIC	
SAMP.	COUNTY	STATE	NAME	NO.	COUNTY	STATE	(MILLIONS OF TONS	SAMPLE	YIELD	ASH	SULFUR	SULFUR
								CONFORM				
1	2	3	4	5	6	7	8	9	10	11	12	13
17	JEFFERSON	OHIO	WAYNESBURG		23	N/L	337.86	8.33	7.9	1.9	1.42	0.28
124	SOMERSET	PA	PITTSBURGH (TOP)		36	19.53	3943.32	3.33	0.7	1.8	0.88	0.15
141	ALLEGANY	MARYLAND	FRANKLIN (BOTTOM)		42			28.57	4.9	1.4	1.05	0.03
142	ALLEGANY	MARYLAND	FRANKLIN (BOTTOM)		42			28.57	11.4	2.0	1.23	0.20
169	COLUMBIANA	OHIO	UPPER FREEPORT		71	686.30	2750.70	25.00	53.9	1.9	0.50	0.03
193	ARMSTRONG	PA	UPPER FREEPORT		71	396.90	4678.60	3.23	60.5	2.0	0.53	0.09
228	SOMERSET	PA	LOWER FREEPORT		74	129.36	2251.05	22.22	1.1	1.2	0.53	0.07
229	SOMERSET	PA	LOWER FREEPORT		74	129.36	2251.05	22.22	31.2	1.6	0.66	0.04
230	SOMERSET	PA	LOWER FREEPORT		74	129.36	2251.05	22.22	32.2	1.9	0.49	0.12
231	SOMERSET	PA	LOWER FREEPORT		74	129.36	2251.05	22.22	33.5	1.9	0.68	0.01
237	CAMBRIA	PA	UPPER KITTANNING		76	377.67	1066.37	23.08	7.0	2.0	0.60	0.04
242	SOMERSET	PA	UPPER KITTANNING		76	454.59	1066.37	23.08	19.7	1.9	1.01	0.07
243	CAMBRIA	PA	UPPER KITTANNING		76	377.67	1066.37	23.08	11.0	1.7	0.49	0.03
253	COSHOCTON	OHIO	MIDDLE KITTANNING		80	270.19	5989.08	25.00	52.2	1.9	2.13	0.40
260	VINTON	OHIO	MIDDLE KITTANNING		80	112.12	5989.08	25.00	70.8	1.6	0.84	0.10
265	COLUMBIANA	OHIO	MIDDLE KITTANNING		80	46.84	5989.08	25.00	59.5	1.6	0.86	0.19
267	TUSCARAWAS	OHIO	MIDDLE KITTANNING		80	745.14	5989.08	25.00	63.9	2.0	1.91	0.18
270	MUSKINGHAM	OHIO	MIDDLE KITTANNING		80	620.27	5989.08	25.00	65.7	2.0	2.32	0.65
272	HOLMES	OHIO	MIDDLE KITTANNING		80	7.55	5989.08	25.00	57.0	1.9	1.36	0.60
273	COLUMBIANA	OHIO	MIDDLE KITTANNING		80	46.84	5989.08	25.00	64.9	1.4	0.59	0.10
278	CLARION	PA	MIDDLE KITTANNING		80	11.71	826.41	31.25	35.4	2.0	0.71	0.05
282	CLEARFIELD	PA	MIDDLE KITTANNING		80	95.88	826.41	31.25	49.4	2.0	0.93	0.09
288	SOMERSET	PA	MIDDLE KITTANNING		80	91.04	826.41	31.25	0.7	2.0	0.67	0.12
290	BUTLER	PA	MIDDLE KITTANNING		80	336.62	826.41	31.25	61.9	1.2	0.50	0.04
291	SOMERSET	PA	MIDDLE KITTANNING		80	91.04	826.41	31.25	20.4	1.7	0.64	0.08
300	TUSCARAWAS	OHIO	LOWER KITTANNING		84	225.66	1936.20	22.73	39.9	1.7	2.12	0.44
301	MAHONING	OHIO	LOWER KITTANNING		84	317.53	1936.20	22.73	89.3	1.3	0.59	0.11
303	MAHONING	OHIO	LOWER KITTANNING		84	317.53	1936.20	22.73	83.5	1.0	0.57	0.05
306	HOLMES	OHIO	LOWER KITTANNING		84	58.86	1936.20	22.73	71.4	1.8	2.08	0.24
314	TUSCARAWAS	OHIO	LOWER KITTANNING #5		84	225.66	1936.20	22.73	61.2	2.0	2.43	0.50
327	BEDFORD	PA	LOWER KITTANNING		84	27.55	3071.99	6.98	39.5	1.3	0.76	0.04
348	CAMBRIA	PA	LOWER KITTANNING		84	365.17	3071.99	6.98	44.0	2.0	0.63	0.03
357	JEFFERSON	PA	LOWER KITTANNING		84	170.47	3071.99	6.98	55.6	1.9	1.38	0.38
361	BUTLER	PA	UPPER CLARION		86	N/L	13.46	100.00	72.1	1.6	1.68	0.38
367	CENTRE	PA	CLARION		87	75.54	943.41	50.00	49.3	1.7	0.77	0.05
368	CLARION	PA	CLARION		87	386.44	943.41	50.00	46.3	1.9	1.63	0.33
369	VENANGO	PA	CLARION		87	18.61	943.41	50.00	37.5	1.8	1.87	0.07
370	MAHONING	OHIO	BROOKVILLE		95	N/L	241.84	66.67	66.7	1.5	0.85	0.18
372	STARK	OHIO	BROOKVILLE		95	148.84	241.84	66.67	77.4	1.5	2.62	0.55
373	LAWRENCE	PA	BROOKVILLE		95	0.87	710.30	50.00	89.2	0.9	0.52	0.07
374	CENTRE	PA	BROOKVILLE		95	84.02	710.30	50.00	44.1	1.5	0.66	0.03
376	BUTLER	PA	BROOKVILLE		95	2.94	710.30	50.00	10.6	1.6	1.07	0.04
377	LAWRENCE	PA	BROOKVILLE		95	0.87	710.30	50.00	66.5	1.8	0.75	0.12
382	MERCER	PA	BROOKVILLE		95	56.45	710.30	50.00	72.1	1.7	1.71	0.29
387	TIOGA	PA	UNCORRELATED (TOP)		799	-	-	-	22.7	1.6	0.60	0.01
392	CAMPBELL	TENN	JORDAN		144	10.07	10.99	100.00	51.7	1.6	0.67	0.03
393	CLAIBORNE	TENN	JELICO		151	6.07	47.21	100.00	57.3	1.6	0.66	0.06

TABLE 1 (Continued)
Less than 2% Ash

A-4

DOE SAMP.		COUNTY	STATE	COALBED NAME	BED NO.	ESTIMATED RESERVES		1.30 FLOAT 14M X 100M		TOTAL SULFUR	PYRITIC SULFUR	
						COUNTY	STATE	SAMPLE CONFORM %	YIELD	ASH		
						(MILLIONS OF TONS)						
1	2	3	4	5	6	7	8	9	10	11	12	13
394	CAMPBELL	TENN	JELICO (TOP)		151	18.81	47.21	100.00	64.6	1.5	0.76	0.10
395	CAMPBELL	TENN	JELICO (BOTTOM)		151	18.81	47.21	100.00	61.0	1.9	0.93	0.25
396	WISE	VA	TAGGART		151	52.41	86.18	100.00	64.7	1.4	0.72	0.09
398	WISE	VA	IMBODEN (BOTTOM)		168	33.55	88.72	100.00	80.7	1.3	0.86	0.14
399	WISE	VA	DORCHESTER		185	79.99	94.22	100.00	92.0	0.8	0.82	0.09
402	DICKENSON	VA	SPLASH DAM		210	51.56	365.41	100.00	42.9	2.0	0.80	0.07
410	BLOUNT	ALA	BLACK CREEK		299	0.72	71.52	100.00	75.7	1.2	0.70	0.04
411	MARION	ALA	BLACK CREEK		299	N/L	71.52	100.00	87.0	1.7	0.79	0.13
412	MARION	ALA	BLACK CREEK		299	N/L	71.52	100.00	72.2	1.8	0.83	0.23
413	JEFFERSON	ALA	BLACK CREEK		299	21.22	71.52	100.00	87.0	1.0	0.56	0.07
414	CULLMAN	ALA	BLACK CREEK		299	32.11	71.52	100.00	86.5	0.8	0.60	0.05
486	FRANKLIN	ILL	NO. 6		484	1875.68	35614.77	3.57	22.5	2.0	0.87	0.20
559	WAGONER	OKLA	SECOR		527	N/L	57.92	100.00	88.8	1.4	0.51	0.16
585	HASKELL	OKLA	STIGLER		556	41.54	59.47	50.00	88.2	1.9	0.56	0.01
595	MAHASKA	IOWA	UNCORRELATED		799	-	-	-	8.9	1.1	0.87	0.05
673	SWEETWATER	WYOM	ROCK SPRINGS #8		506			100.00	47.1	1.5	0.83	0.07
725	GUNNISON	COLO	C		754	103.04	140.90	100.00	72.0	2.0	0.43	0.09
726	GUNNISON	COLORADO	C		754	103.04	140.90	100.00	71.1	1.6	0.35	0.04
727	GARFIELD	COLORADO	COAL BASIN D		755	16.40	83.13	50.00	65.2	1.5	0.60	0.03
729	GUNNISON	COLORADO	E		756	48.88	83.64	100.00	80.9	1.3	0.33	0.07
738	MOFFAT	COLORADO	COLLUM		769	N/L	N/L	100.00	40.2	1.9	0.25	0.01
755	SWEETWATER	WYOM	ROCK SPRINGS #3		790			100.00	60.7	2.0	0.82	0.08
756	SWEETWATER	WYOM	ROCK SPRINGS #9		793			100.00	71.3	1.3	1.03	0.23
757	SWEETWATER	WYOM	ROCK SPRINGS #11		796			100.00	69.5	1.8	0.80	0.06
766	CARBON	UTAH	LOWER SUNNYSIDE		802	N/L	N/L	100.00	59.5	1.8	0.55	0.04
792	CARBON	UTAH	A SEAM (HIAWATHA)		846	N/L	N/L	33.33	76.8	2.0	0.56	0.07
796	SEVIER	UTAH	HIAWATHA		846	N/L	N/L	33.33	35.6	1.8	0.45	0.09
801	CARBON	UTAH	B SEAM (BEAR CANYON)		856	N/L	N/L	100.00	78.7	1.8	0.58	0.06
841	HOPKINS	KY (WEST)	NO. 6		506	18.51	506.38	100.00	25.9	1.3	1.16	0.27
842	HOPKINS	KY (WEST)	NO. 6		506	18.51	506.38	100.00	68.9	1.8	1.14	0.32
843	BUTLER	KY (WEST)	NO. 6		506	N/L	506.38	100.00	50.0	1.3	0.87	0.17
844	OHIO	KY (WEST)	NO. 6		506	13.99	506.38	100.00	60.9	1.6	0.83	0.27
853	BREATHITT	KY (EAST)	HAZARD 5A		111	76.68	1097.43	50.00	74.8	1.0	0.75	0.00
855	BELL	KY (EAST)	HAZARD NO. 4		135	36.27	1663.06	50.00	51.1	1.9	0.95	0.10
860	MCCREARY	KY (EAST)	UPPER ELKHORN #3		151	0.40	2059.31	100.00	66.7	1.3	0.91	0.16
861	MORGAN	KY (EAST)	UPPER ELKHORN #3		151	14.67	2059.31	100.00	82.9	0.7	0.54	0.01
862	FLOYD	KY (EAST)	UPPER ELKHORN #2		154	249.01	1199.31	100.00	73.6	1.3	0.79	0.10
863	LAUREL	KY (EAST)	UPPER ELKHORN #1		157	N/L	1091.37	100.00	65.1	1.1	0.73	0.09
864	LAUREL	KY (EAST)	UPPER ELKHORN #1		157	N/L	1091.37	100.00	81.3	1.3	0.67	0.06
870	KANAWHA	WV	WINIFREDE		121	85.50	969.43	75.00	65.9	1.9	0.62	0.02
871	BOONE	WV	WINIFREDE		121	455.03	969.43	75.00	50.0	1.6	0.79	0.12
873	KANAWHA	WV	WINIFREDE		121	85.50	969.43	75.00	63.2	1.4	0.69	0.09
874	LOGAN	WV	CHILTON		135	249.54	775.82	100.00	31.7	1.3	0.72	0.01
877	MINGO	WV	NO. 2 GAS		168	156.34	2516.62	100.00	69.3	1.2	0.76	0.07
878	LOGAN	WV	POWELTON		170	0.82	206.32	100.00	53.3	1.3	0.69	0.01
879	MCDOWELL	WV	LOWER WAR EAGLE		195			100.00	58.2	1.9	0.70	0.08

TABLE 1 (Continued)

A-5

Less than 2.0% Ash

		1.30 FLOAT 14M X 100M					1.40 FLOAT 14M X 100M					#SO2/ M BTU	
DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	YIELD	ASH	TOTAL SULFUR	BTU/LB			
1	2	5	10	11	12	13	14	15	16	17	18	19	20
17	WAYNESBURG	7.9	1.9	1.42	0.28	14410	1.971	51.7	7.4	2.02	13490	2.995	
124	PITTSBURGH (TOP)	0.7	1.8	0.88	0.15	14374	1.224	51.0	5.2	0.77	13825	1.114	
141	FRANKLIN (BOTTOM)	4.9	1.4	1.05	0.03	15086	1.392	61.6	6.3	0.99	14326	1.382	
142	FRANKLIN (BOTTOM)	11.4	2.0	1.23	0.20	15091	1.630	61.5	6.2	1.70	14434	2.356	
169	UPPER FREEPORT	53.9	1.9	0.50	0.03	14634	0.683	82.3	3.9	0.52	14310	0.727	
193	UPPER FREEPORT	60.5	2.0	0.53	0.09	14868	0.713	86.2	3.6	0.56	14599	0.767	
228	LOWER FREEPORT	1.1	1.2	0.53	0.07	14641	0.724	67.5	3.2	0.55	14377	0.765	
229	LOWER FREEPORT	31.2	1.6	0.66	0.04	15300	0.863	87.4	3.5	0.60	14980	0.801	
230	LOWER FREEPORT	32.2	1.9	0.49	0.12	15284	0.641	78.6	3.9	0.54	14934	0.723	
231	LOWER FREEPORT	33.5	1.9	0.68	0.01	15336	0.887	86.4	3.6	0.67	15052	0.890	
237	UPPER KITTANNING	7.0	2.0	0.60	0.04	14851	0.808	46.6	5.7	0.62	14288	0.868	
242	UPPER KITTANNING	19.7	1.9	1.01	0.07	15227	1.327	69.5	4.8	0.96	14736	1.303	
243	UPPER KITTANNING	11.0	1.7	0.49	0.03	15170	0.646	71.3	4.2	0.55	14755	0.746	
253	MIDDLE KITTANNING	52.2	1.9	2.13	0.40	14157	3.009	71.4	2.7	2.54	14020	3.623	
260	MIDDLE KITTANNING	70.8	1.6	0.84	0.10	13884	1.210	94.2	2.4	0.82	13771	1.191	
265	MIDDLE KITTANNING	59.5	1.6	0.86	0.19	14758	1.165	76.5	2.8	1.02	14538	1.403	
267	MIDDLE KITTANNING	63.9	2.0	1.91	0.18	14234	2.684	82.4	3.0	2.19	14055	3.116	
270	MIDDLE KITTANNING	65.7	2.0	2.32	0.65	14280	3.249	85.0	2.9	2.79	14119	3.952	
272	MIDDLE KITTANNING	57.0	1.9	1.36	0.60	14265	1.907	84.1	3.0	1.92	14062	2.731	
273	MIDDLE KITTANNING	64.9	1.4	0.59	0.10	14861	0.794	85.9	2.5	0.68	14671	0.927	
278	MIDDLE KITTANNING	35.4	2.0	0.71	0.05	14465	0.982	83.3	3.8	0.68	14201	0.958	
282	MIDDLE KITTANNING	49.4	2.0	0.93	0.09	15045	1.236	81.6	3.9	0.94	14729	1.276	
288	MIDDLE KITTANNING	0.7	2.0	0.67	0.12	14937	0.897	50.9	9.3	0.40	13718	0.583	
290	MIDDLE KITTANNING	61.9	1.2	0.50	0.04	14584	0.686	91.2	2.1	0.50	14441	0.692	
291	MIDDLE KITTANNING	20.4	1.7	0.64	0.08	15230	0.840	74.0	5.0	0.66	14671	0.900	
300	LOWER KITTANNING	39.9	1.7	2.12	0.44	14898	2.846	74.9	3.0	2.79	14664	3.805	
301	LOWER KITTANNING	89.3	1.3	0.59	0.11	14597	0.808	94.3	1.6	0.68	14552	0.935	
303	LOWER KITTANNING	83.5	1.0	0.57	0.05	14671	0.777	92.7	1.4	0.60	14605	0.822	
306	LOWER KITTANNING	71.4	1.8	2.08	0.24	14220	2.925	86.9	2.6	2.25	14085	3.195	
314	LOWER KITTANNING #5	61.2	2.0	2.43	0.50	14104	3.446	81.2	2.8	2.71	13965	3.881	
327	LOWER KITTANNING	39.5	1.3	0.76	0.04	15457	0.983	76.9	3.4	0.80	15114	1.059	
348	LOWER KITTANNING	44.0	2.0	0.63	0.03	15250	0.826	74.1	4.1	0.62	14889	0.833	
357	LOWER KITTANNING	55.6	1.9	1.38	0.38	15205	1.815	72.2	3.3	1.64	14959	2.193	
361	UPPER CLARION	72.1	1.6	1.68	0.38	14837	2.265	82.2	2.3	1.70	14714	2.311	
367	CLARION	49.3	1.7	0.77	0.05	15189	1.014	74.0	3.7	0.79	14845	1.064	
368	CLARION	46.3	1.9	1.63	0.33	14942	2.182	63.7	3.5	2.21	14648	3.017	
369	CLARION	37.5	1.8	1.87	0.07	14410	2.595	65.9	3.6	1.84	14118	2.607	
370	BROOKVILLE	66.7	1.5	0.85	0.18	15115	1.125	85.8	2.9	0.93	14895	1.249	
372	BROOKVILLE	77.4	1.5	2.62	0.55	14333	3.656	87.4	2.1	2.77	14233	3.892	
373	BROOKVILLE	89.2	0.9	0.52	0.07	14650	0.710	93.0	1.3	0.57	14596	0.781	
374	BROOKVILLE	44.1	1.5	0.66	0.03	15324	0.861	72.7	2.7	0.67	15120	0.886	
376	BROOKVILLE	10.6	1.6	1.07	0.04	13768	1.554	83.3	3.6	0.82	13477	1.217	
377	BROOKVILLE	66.5	1.8	0.75	0.12	14587	1.028	85.5	3.0	0.98	14379	1.363	
382	BROOKVILLE	72.1	1.7	1.71	0.29	14595	2.343	84.7	2.5	1.86	14442	2.576	
387	UNCORRELATED (TOP)	22.7	1.6	0.60	0.01	15250	0.787	70.7	4.7	0.61	14700	0.830	
392	JORDAN	51.7	1.6	0.67	0.03	14579	0.919	92.6	2.4	0.68	14461	0.940	
393	JELLICO	57.3	1.6	0.66	0.06	14643	0.901	80.7	3.1	0.71	14420	0.985	

TABLE 1 (Continued)

A-6

Less than 2.0% Ash

		1.30 FLOAT 14M X 100M					1.40 FLOAT 14M X 100M						
DOE	COALBED			TOTAL	PYRITIC					TOTAL		#SO2/	
SAMP.	NAME	YIELD	ASH	SULFUR	SULFUR	BTU/LB		YIELD	ASH	SULFUR	BTU/LB	M BTU	
1	2	5	10	11	12	13	14	15	16	17	18	19	20
394	JELLICO (TOP)	64.6	1.5	0.76	0.10	14543	1.045	96.9	1.7	0.77	14513	1.061	
395	JELLICO (BOTTOM)	61.0	1.9	0.93	0.25	14485	1.284	89.6	2.4	0.96	14412	1.332	
396	TAGGART	64.7	1.4	0.72	0.09	14792	0.973	95.6	2.1	0.73	14695	0.994	
398	IMBODEN (BOTTOM)	80.7	1.3	0.86	0.14	15013	1.146	94.7	2.3	0.92	14860	1.238	
399	DORCHESTER	92.0	0.8	0.82	0.09	15006	1.093	97.9	1.0	0.82	14975	1.095	
402	SPLASH DAM	42.9	2.0	0.80	0.07	15082	1.061	62.9	3.6	0.79	14835	1.065	
410	BLACK CREEK	75.7	1.2	0.70	0.04	15380	0.910	87.3	1.8	0.70	15387	0.910	
411	BLACK CREEK	87.0	1.7	0.79	0.13	14435	1.095	94.9	1.9	0.81	14405	1.125	
412	BLACK CREEK	72.2	1.8	0.83	0.23	14331	1.158	92.9	2.2	0.94	14272	1.317	
413	BLACK CREEK	87.0	1.0	0.56	0.07	15306	0.732	92.6	1.1	0.56	15291	0.732	
414	BLACK CREEK	86.5	0.8	0.60	0.05	14943	0.803	97.1	1.2	0.60	14881	0.806	
486	NO. 6	22.5	2.0	0.87	0.20	14038	1.239	72.3	4.8	0.91	13636	1.335	
559	SECOR	88.8	1.4	0.51	0.16	14886	0.685	96.5	1.6	0.56	14854	0.754	
585	STIGLER	88.2	1.9	0.56	0.01	15336	0.730	93.8	2.1	0.57	15305	0.745	
595	UNCORRELATED	8.9	1.1	0.87	0.05	14012	1.242	89.2	3.4	0.94	13732	1.369	
673	ROCK SPRINGS #8	47.1	1.5	0.83	0.07	12658	1.311	93.4	1.6	0.85	12643	1.345	
725	C	72.0	2.0	0.43	0.09	14054	0.612	88.5	3.1	0.43	13866	0.620	
726	C	71.1	1.6	0.35	0.04	14222	0.492	88.1	2.4	0.37	14084	0.525	
727	COAL BASIN D	65.2	1.5	0.60	0.03	14069	0.853	92.2	2.2	0.62	13961	0.888	
729	E	80.9	1.3	0.33	0.07	14219	0.464	94.8	1.9	0.33	14090	0.468	
738	COLLUM	40.2	1.9	0.25	0.01	13979	0.358	90.5	3.1	0.27	13806	0.391	
755	ROCK SPRINGS #3	60.7	2.0	0.82	0.08	13164	1.246	84.8	2.5	0.85	13082	1.299	
756	ROCK SPRINGS #9	71.3	1.3	1.03	0.23	12784	1.611	94.6	1.3	1.05	12781	1.643	
757	ROCK SPRINGS #11	69.5	1.8	0.80	0.06	13021	1.229	91.1	1.9	0.81	13006	1.246	
766	LOWER SUNNYSIDE	59.5	1.8	0.55	0.04	14600	0.753	86.7	3.4	0.54	14307	0.755	
792	A SEAM (HIAWATHA)	76.8	2.0	0.56	0.07	14287	0.784	90.8	2.7	0.56	14172	0.790	
796	HIAWATHA	35.6	1.8	0.45	0.09	13480	0.668	86.7	2.8	0.43	13303	0.646	
801	B SEAM (BEAR CANYON)	78.7	1.8	0.58	0.06	14610	0.794	90.7	2.6	0.58	14451	0.803	
841	NO. 6	25.9	1.3	1.16	0.27	14049	1.651	70.0	2.6	1.35	13864	1.947	
842	NO. 6	68.9	1.8	1.14	0.32	14113	1.616	84.7	2.6	1.22	13998	1.743	
843	NO. 6	50.0	1.3	0.87	0.17	14070	1.237	65.8	2.2	0.98	13941	1.406	
844	NO. 6	60.9	1.6	0.83	0.27	14300	1.161	84.2	2.7	1.06	14133	1.500	
853	HAZARD 5A	74.8	1.0	0.75	0.00	14519	1.033	94.1	1.4	0.73	14455	1.010	
855	HAZARD NO. 4	51.1	1.9	0.95	0.10	14578	1.303	67.9	3.1	1.05	14396	1.459	
860	UPPER ELKHORN #3	66.7	1.3	0.91	0.16	14623	1.245	82.2	2.0	1.04	14517	1.433	
861	UPPER ELKHORN #3	82.9	0.7	0.54	0.01	14566	0.741	96.7	1.0	0.55	14518	0.758	
862	UPPER ELKHORN #2	73.6	1.3	0.79	0.10	14555	1.086	90.2	2.0	0.84	14450	1.163	
863	UPPER ELKHORN #1	65.1	1.1	0.73	0.09	14750	0.990	93.3	1.8	0.76	14634	1.039	
864	UPPER ELKHORN #1	81.3	1.3	0.67	0.06	14780	0.907	92.6	1.8	0.68	14697	0.925	
870	WINIFREDE	65.9	1.9	0.62	0.02	14561	0.852	84.9	2.6	0.61	14458	0.844	
871	WINIFREDE	50.0	1.6	0.79	0.12	14748	1.071	60.7	2.6	0.83	14595	1.137	
873	WINIFREDE	63.2	1.4	0.69	0.09	14719	0.938	89.6	2.5	0.67	14552	0.921	
874	CHILTON	31.7	1.3	0.72	0.01	14998	0.960	87.8	2.4	0.65	14831	0.877	
877	NO. 2 GAS	69.3	1.2	0.76	0.07	14747	1.031	87.9	2.1	0.91	14612	1.246	
878	POWELTON	53.3	1.3	0.69	0.01	15047	0.917	73.2	2.5	0.76	14863	1.023	
879	LOWER WAR EAGLE	58.2	1.9	0.70	0.08	15112	0.926	83.6	3.5	0.72	14867	0.969	

TABLE 1 (Continued)

A-7

Less than 2.0% Ash

		1.30 FLOAT 3/8" X 100M					1.60 FLOAT CLEAN COAL					ASH FUSION TEMP			
DOE		COALBED			TOTAL		#S02/	MAF	FUEL			FSI	SOFT	DEFORM	FLUID
SAMP.		NAME	YIELD	ASH	SULFUR	BTU/LB	M BTU	F.CARBON	RATIO	HGI					
1	2	5	21	22	23	24	25	26	27	28	29	30	31	32	
17		WAYNESBURG	5.5	2.5	0.92	14358	1.282	56.7	1.31	-	5.0	2150	2210	2540	
124		PITTSBURGH (TOP	1.4	2.3	0.80	14297	1.119	74.6	2.94	-	-	2910	-	-	
141		FRANKLIN (BOTTO	5.9	2.2	1.33	14962	1.778	79.4	3.85	-	2.0	2700	2750	2820	
142		FRANKLIN (BOTTO	9.3	2.9	1.50	14950	2.007	79.1	3.78	-	9.0	2520	2610	2700	
169		UPPER FREEPORT	57.8	2.6	0.56	14516	0.772	60.3	1.52	50	6.0	2680	2810	2910	
193		UPPER FREEPORT	65.1	2.1	0.63	14843	0.849	63.7	1.75	-	8.5	2910	-	-	
228		LOWER FREEPORT	0.8	3.2	0.52	14378	0.723	76.5	3.26	99	1.5	2780	2830	2890	
229		LOWER FREEPORT	27.2	1.8	0.65	15266	0.852	79.4	3.85	104	9.0	2910	-	-	
230		LOWER FREEPORT	37.2	2.2	0.53	15227	0.696	80.1	4.03	90	9.0	2910	-	-	
231		LOWER FREEPORT	35.0	2.0	0.70	15318	0.914	78.7	3.69	106	9.0	2910	-	-	
237		UPPER KITTANNIN	15.1	2.3	0.60	14805	0.811		0.00						
242		UPPER KITTANNIN	27.3	2.0	0.99	15212	1.302	79.2	3.81	-	9.0	2910	-	-	
243		UPPER KITTANNIN	15.4	1.7	0.61	15161	0.805	82.5	4.71	-	4.0	2910	-	-	
253		MIDDLE KITTANNI	51.9	2.1	2.19	14126	3.101	53.5	1.15	-	4.0	2030	2080	2250	
260		MIDDLE KITTANNI	84.1	2.1	0.84	13812	1.216	56.4	1.29	44	2.0	-	-	-	
265		MIDDLE KITTANNI	61.6	2.6	1.05	14572	1.441	60.8	1.55	59	6.5	2150	2200	2390	
267		MIDDLE KITTANNI	63.6	2.1	1.87	14221	2.630	52.3	1.10	42	3.5	2050	2100	2150	
270		MIDDLE KITTANNI	69.8	2.5	2.18	14221	3.066	51.4	1.06	43	2.5	2410	2460	2560	
272		MIDDLE KITTANNI	56.7	2.2	1.50	14221	2.110	54.5	1.20	48	3.5	1980	2020	2060	
273		MIDDLE KITTANNI	64.6	2.0	0.69	14755	0.935	61.3	1.58	62	7.5	2910	2910	2910	
278		MIDDLE KITTANNI	68.3	2.8	0.71	14348	0.990		0.00						
282		MIDDLE KITTANNI	53.2	2.6	0.93	14945	1.245	74.6	2.94	-	9.0	2840	2910	-	
288		MIDDLE KITTANNI	0.4	9.2	0.64	13715	0.933	80.3	4.08	79	1.5	2910	-	-	
290		MIDDLE KITTANNI	83.1	1.9	0.48	14475	0.663	58.3	1.40	47	4.5	2910	-	-	
291		MIDDLE KITTANNI	22.0	2.0	0.62	15180	0.817	78.5	3.65	107	55.0	2910	-	-	
300		LOWER KITTANNIN	50.8	1.9	2.14	14867	2.879	54	1.17	-	-	-	-	-	
301		LOWER KITTANNIN	85.4	1.5	0.65	14571	0.892	59.4	1.46	52	5.0	-	-	-	
303		LOWER KITTANNIN	87.4	1.5	0.64	14588	0.877	60.2	1.51	56	7.0	2370	2450	2670	
306		LOWER KITTANNIN	66.9	1.9	1.89	14221	2.658	51.1	1.04	49	4.0	2050	2110	2150	
314		LOWER KITTANNIN	56.9	1.9	2.33	14127	3.299	54.2	1.18	55	2.5	2010	2060	2110	
327		LOWER KITTANNIN	38.6	1.7	0.74	15394	0.961	86.4	6.35	-	9.0	2910	-	-	
348		LOWER KITTANNIN	44.5	2.4	0.65	15179	0.856	77.8	3.50	93	9.0	2910	-	-	
357		LOWER KITTANNIN	54.9	3.0	1.60	15006	2.132	62.3	1.65	68	8.0	2190	2290	2480	
361		UPPER CLARION	72.8	1.8	1.65	14798	2.230	56.2	1.28	59	7.5	1980	2030	2300	
367		CLARION	53.8	2.1	0.99	15103	1.311	75.9	3.15	99	9.0	2910	-	-	
368		CLARION	54.3	2.4	2.02	14836	2.723	54.1	1.18	48	8.0	2050	2100	2150	
369		CLARION	51.1	2.6	1.84	14282	2.577	56.6	1.30	57	5.0	2550	2600	2650	
370		BROOKVILLE	66.5	1.5	0.85	15115	1.125	53.1	1.13						
372		BROOKVILLE	80.6	1.8	2.42	14307	3.383	53.6	1.16	47	5.5	2060	2150	2250	
373		BROOKVILLE	86.2	1.7	0.70	14536	0.963	59.8	1.49	-	5.5	2560	2610	2680	
374		BROOKVILLE	56.1	2.0	0.67	15239	0.879	74.3	2.89	-	9.0	2910	-	-	
376		BROOKVILLE	7.8	1.7	1.07	13752	1.556	62.7	1.68	54	-	2900	2910	-	
377		BROOKVILLE	70.9	2.2	0.71	14525	0.978	58.2	1.39	49	6.5	2460	2570	2670	
382		BROOKVILLE	71.4	2.3	1.65	14493	2.277	53.6	1.16	45	5.5	2000	2130	2430	
387		UNCORRELATED (T	27.9	2.1	0.56	15165	0.739	80	4.00	-	9.0	2910	-	-	
392		JORDAN	71.1	1.7	0.68	14564	0.934		0.00						
393		JELICO	71.3	1.8	0.69	14613	0.944		0.00						

TABLE 1 (Continued)

A-8

Less than 2.0% Ash

		1.30 FLOAT 3/8" X 100M				1.60 FLOAT CLEAN COAL								
DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	BTU/LB	#502/ M BTU	MAF F.CARBON	FUEL RATIO	HGI	FSI	ASH FUSION TEMP SOFT	DEFORM	FLUID	
1	2	5	21	22	23	24	25	26	27	28	29	30	31	32
394	JELICO (TOP)	88.0	1.5	0.79	14543	1.086	60.3	1.52	39	3.5	2090	2140	2250	
395	JELICO (BOTTOM	77.8	2.0	0.95	14471	1.313	60	1.50	40	5.0	2520	2570	2620	
396	TAGGART	70.6	1.8	0.71	14736	0.964	63.9	1.77	48	5.5	2480	2580	2780	
398	IMBODEN (BOTTOM	81.4	1.5	0.88	14982	1.175	65.7	1.92	53	9.0	2780	2830	2880	
399	DORCHESTER	95.0	1.1	0.85	14960	1.136	63.7	1.75	55	9.0	2030	2080	2130	
402	SPLASH DAM	49.1	2.3	0.79	15035	1.051	67.4	2.07	-	8.5	2910	-	-	
410	BLACK CREEK	82.6	1.4	0.71	15349	0.925	65.8	1.92	-	-	-	-	-	
411	BLACK CREEK	88.3	1.7	0.80	14435	1.108	58.9	1.43	37	4.0	2410	3460	2510	
412	BLACK CREEK	86.3	2.1	0.91	14286	1.274	59.3	1.46	38	3.5	2360	2410	2460	
413	BLACK CREEK	88.1	1.1	0.61	15291	0.798	68	2.13	66	9.0	2910	-	-	
414	BLACK CREEK	92.9	1.2	0.63	14881	0.847	61.3	1.58	41	7.0	2910	-	-	
486	NO. 6	53.5	3.0	0.91	13894	1.310		0.00						
559	SECOR	94.7	1.7	0.58	14837	0.782	63.8	1.76	45	6.5	2090	2220	2360	
585	STIGLER	89.7	2.1	0.58	15304	0.758	71.9	2.56	-	-	-	-	-	
595	UNCORRELATED	69.7	3.3	1.10	13737	1.602	54.2	1.18	-	3.0	2250	2350	2600	
673	ROCK SPRINGS #8	69.1	1.5	0.84	12659	1.327	52.6	1.11	48	-	2350	2410	2460	
725	C	72.9	2.4	0.42	13985	0.601	57.2	1.34	41	1.0	2690	2790	2910	
726	C	85.3	2.3	0.34	14103	0.482	59	1.44	45	2.0	2780	2830	2910	
727	COAL BASIN D	85.0	1.7	0.51	14046	0.726	57.8	1.37	53	1.5	-	2800	-	
729	E	85.3	2.2	0.34	14026	0.485	58.6	1.42	43	1.5	2370	2420	2520	
738	COLLUM	52.9	2.3	0.26	13921	0.374	54.3	1.19	-	-	-	-	-	
755	ROCK SPRINGS #3	73.7	2.3	0.86	13113	1.312	54.4	1.19	44	-	2080	2130	2180	
756	ROCK SPRINGS #9	82.0	1.5	1.10	12750	1.725	53.8	1.16	50	-	2030	2080	2170	
757	ROCK SPRINGS #1	77.5	1.7	0.85	13032	1.304	54.3	1.19	49	-	2080	2140	2190	
766	LOWER SUNNYSIDE	68.0	2.7	0.53	14436	0.734	59.8	1.49	49	3.0	-	2270	-	
792	A SEAM (HIAWATH	80.5	2.5	0.59	14202	0.831	53.4	1.15	48	3.0	-	2100	-	
796	HIAWATHA	39.3	2.6	0.45	13335	0.675	56.6	1.30	50	-	2090	2140	2190	
801	B SEAM (BEAR CA	83.3	2.2	0.59	14530	0.812	53.5	1.15	48	3.0	-	2180	-	
841	NO. 6	40.2	1.7	1.23	13992	1.758	58.6	1.42	-	-	-	-	-	
842	NO. 6	80.4	1.9	1.15	14099	1.631	59.3	1.46	-	-	-	-	-	
843	NO. 6	60.6	1.6	0.92	14027	1.312	55.7	1.26	-	-	-	-	-	
844	NO. 6	73.5	2.1	0.82	14224	1.153	57.5	1.35	47	3.5	2140	2190	2290	
853	HAZARD 5A	93.9	1.4	0.56	14455	0.775	60.7	1.54	43	2.0	2840	2910	-	
855	HAZARD NO. 4	53.0	2.2	0.84	14532	1.156	57.2	1.34	43	4.0	2630	2730	2830	
860	UPPER ELKHORN #	72.9	1.7	0.90	14563	1.236	60.4	1.53	41	4.5	2250	2300	2360	
861	UPPER ELKHORN #	90.6	1.2	0.48	14485	0.663	59.9	1.49	38	1.5	2720	2770	2820	
862	UPPER ELKHORN #	71.5	1.4	0.79	14540	1.087	61.1	1.57	39	3.0	2620	2680	2780	
863	UPPER ELKHORN #	86.4	1.6	0.79	14668	1.077	57.5	1.35	46	5.0	2910	-	-	
864	UPPER ELKHORN #	80.7	1.2	0.78	14797	1.054	59	1.44	45	5.0	2680	2730	2780	
870	WINIFREDE	62.3	1.6	0.63	14605	0.863	59.2	1.45	-	5.5	2910	-	-	
871	WINIFREDE	52.6	2.0	0.70	14687	0.953	60	1.50	41	7.5	2880	2910	-	
873	WINIFREDE	69.7	1.7	0.72	14673	0.981	59.8	1.49	37	4.0	2910	-	-	
874	CHILTON	76.8	1.9	0.66	14907	0.885	64.7	1.83	-	8.5	2910	-	-	
877	NO. 2 GAS	75.6	1.5	0.89	14702	1.211	58.1	1.39	39	5.5	2530	2580	2630	
878	POWELTON	66.4	1.7	0.70	14986	0.934	67	2.03	-	9.0	2910	-	-	
879	LOWER WAR EAGLE	65.8	2.4	0.71	15035	0.944	65.4	1.89	65	8.5	2910	-	-	

TABLE 2

A-9

Less than 1.5% Ash

DOE					ESTIMATED RESERVES		1.30 FLOAT 14M X 100M				PYRITIC	
SAMP.	COUNTY	STATE	COALBED	NAME	NO.	COUNTY	STATE	SAMPLE	YIELD	ASH	TOTAL	SULFUR
						(MILLIONS OF TONS)		CONFORM			SULFUR	SULFUR
								%				
1	2	3	4	5	6	7	8	9	10	11	12	13
273	COLUMBIANA	OHIO	MID. KITT		80	46.84	5989.08	3.57	64.9	1.4	0.59	0.10
290	BUTLER	PA	MID. KITT		80	336.62	826.41	6.25	61.9	1.2	0.50	0.04
301	MAHONING	OHIO	LOW. KITT		84	317.53	1932.20	9.09	89.3	1.3	0.59	0.11
303	MAHONING	OHIO	LOW. KITT		84	317.53	1932.20	9.09	83.5	1.0	0.57	0.05
327	BEDFORD	PENNA	LOW. KITT		84	27.55	3071.99	2.33	39.5	1.3	0.76	0.04
370	MAHONING	OHIO	BROOKVILLE		95	N/L	241.84	33.33	66.7	1.5	0.85	0.18
373	LAWRENCE	PENNA	BROOKVILLE		95	0.87	710.30	20.00	89.2	0.9	0.52	0.07
374	CENTRE	PENNA	BROOKVILLE		95	84.02	710.30	20.00	44.1	1.5	0.66	0.03
394	CAMPBELL	TENN	JELLICO		151	18.81	47.21	33.33	64.6	1.5	0.76	0.10
396	WISE	VA	TAGGART		151	52.41	86.18	100.00	64.7	1.4	0.72	0.09
398	WISE	VA	IMBODEN		168	33.55	88.72	100.00	80.7	1.3	0.86	0.14
399	WISE	VA	DORCHESTER		185	79.99	94.22	100.00	92.0	0.8	0.82	0.09
410	BLOUNT	ALA	BLACK CREEK		299	0.72	71.52	60.00	75.7	1.2	0.70	0.04
413	JEFFERSON	ALA	BLACK CREEK		299	21.22	71.52	60.00	87.0	1.0	0.56	0.07
414	CULLMAN	ALA	BLACK CREEK		299	32.11	71.52	60.00	86.5	0.8	0.60	0.05
559	WAGONER	OKLA	SECOR		527	N/L	57.92	100.00	88.8	1.4	0.51	0.16
727	GARFIELD	COLO	COAL BASIN D		755	16.40	83.13	100.00	65.2	1.5	0.60	0.03
729	SUNNISON	COLO	COAL BASIN E		756	48.88	83.64	50.00	80.9	1.3	0.33	0.07
841	HOPKINS	KY WEST	NO. 6		506	18.51	506.38	50.00	25.9	1.3	1.16	0.27
843	BUTLER	KY WEST	NO. 6		506	N/L	506.38	50.00	50.0	1.3	0.87	0.17
853	BREATHITT	KY WEST	HAZARD 5A		111	76.68	1097.43	50.00	74.8	1.0	0.75	0.00
860	MC CREARY	KY EAST	UPPER ELKHORN #3		151	0.40	2059.31	100.00	66.7	1.3	0.91	0.16
861	MORGAN	KY EAST	UPPER ELKHORN #3		151	14.67	2059.31	100.00	82.9	0.7	0.54	0.01
862	FLOYD	KY EAST	UPPER ELKHORN #2		154	249.01	1199.31	100.00	73.6	1.3	0.79	0.10
863	LAUREL	KY EAST	UPPER ELKHORN #1		157	N/L	1091.37	100.00	65.1	1.1	0.73	0.09
864	LAUREL	KY EAST	UPPER ELKHORN #1		157	N/L	1091.37	100.00	81.3	1.3	0.67	0.06
873	KANAWHA	WV	WINIFREDE		121	85.50	969.43	25.00	63.2	1.4	0.69	0.09
874	LOGAN	WV	CHILTON		135	249.54	775.92	100.00	31.7	1.3	0.72	0.01
877	MINGO	WV	NO. 2 GAS		168	156.34	2516.62	100.00	69.3	1.2	0.76	0.07
878	LOGAN	WV	POWELTON		170	0.82	206.32	100.00	53.3	1.3	0.69	0.01

TABLE 2 (Continued)

A-10

Less than 1.5% Ash

DOE SAMP.	COALBED NAME	1.30 FLOAT 14M X 100M				1.40 FLOAT 14M X 100M							
		YIELD	ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	#S02/ M BTU	YIELD	ASH	TOTAL SULFUR	BTU/LB	#S02/ M BTU	
1	2	5	10	11	12	13	14	15	16	17	18	19	20
273	MID. KITT		64.9	1.4	0.59	0.10	14861	0.794	85.9	2.5	0.68	14671	0.927
290	MID. KITT		61.9	1.2	0.50	0.04	14584	0.686	91.2	2.1	0.50	14441	0.692
301	LOW. KITT		89.3	1.3	0.59	0.11	14597	0.808	94.3	1.6	0.68	14552	0.935
303	LOW. KITT		83.5	1.0	0.57	0.05	14671	0.777	92.7	1.4	0.60	14605	0.822
327	LOW. KITT		39.5	1.3	0.76	0.04	15457	0.983	76.9	3.4	0.80	15114	1.059
370	BROOKVILLE		66.7	1.5	0.85	0.18	15115	1.125	85.8	2.9	0.93	14895	1.249
373	BROOKVILLE		89.2	0.9	0.52	0.07	14650	0.710	93.0	1.3	0.57	14596	0.781
374	BROOKVILLE		44.1	1.5	0.66	0.03	15324	0.861	72.7	2.7	0.67	15120	0.994
394	JELLICO		64.6	1.5	0.76	0.10	14543	1.045	96.9	1.7	0.77	14513	1.061
396	TAGGART		64.7	1.4	0.72	0.09	14792	0.973	95.6	2.1	0.73	14695	0.994
398	IMBODEN		80.7	1.3	0.86	0.14	15013	1.146	94.7	2.3	0.92	14860	1.238
399	DORCHESTER		92.0	0.8	0.82	0.09	15006	1.093	97.9	1.0	0.82	14975	1.095
410	BLACK CREEK		75.7	1.2	0.70	0.04	15380	0.910	87.3	1.8	0.70	15287	0.916
413	BLACK CREEK		87.0	1.0	0.56	0.07	15306	0.732	92.6	1.1	0.56	15291	0.732
414	BLACK CREEK		86.5	0.8	0.60	0.05	14943	0.803	97.1	1.2	0.60	14881	0.806
559	SECOR		88.8	1.4	0.51	0.16	14886	0.685	96.5	1.6	0.56	14854	0.754
727	COAL BASIN D		65.2	1.5	0.60	0.03	14069	0.853	92.2	2.2	0.62	13961	0.888
729	COAL BASIN E		80.9	1.3	0.33	0.07	14219	0.464	94.8	1.9	0.33	14090	0.468
841	NO. 6		25.9	1.3	1.16	0.27	14049	1.651	70.0	2.6	1.35	13864	1.947
843	NO. 6		50.0	1.3	0.87	0.17	14070	1.237	65.8	2.2	0.98	13941	1.406
853	HAZARD 5A		74.8	1.0	0.75	0.00	14519	1.033	94.1	1.4	0.73	14455	1.010
860	UPPER ELKHORN #3		66.7	1.3	0.91	0.16	14623	1.245	82.2	2.0	1.04	14517	1.433
861	UPPER ELKHORN #3		82.9	0.7	0.54	0.01	14566	0.741	96.7	1.0	0.55	14518	0.758
862	UPPER ELKHORN #2		73.6	1.3	0.79	0.10	14555	1.086	90.2	2.0	0.84	14450	1.163
863	UPPER ELKHORN #1		65.1	1.1	0.73	0.09	14750	0.990	93.3	1.8	0.76	14634	1.039
864	UPPER ELKHORN #1		81.3	1.3	0.67	0.06	14780	0.907	92.6	1.8	0.68	14697	0.925
873	WINIFREDE		63.2	1.4	0.69	0.09	14719	0.938	89.6	2.5	0.67	14552	0.921
874	CHILTON		31.7	1.3	0.72	0.01	14998	0.960	87.8	2.4	0.65	14831	0.877
877	NO. 2 GAS		69.3	1.2	0.76	0.07	14747	1.031	87.9	2.1	0.91	14612	1.246
878	POWELTON		53.3	1.3	0.69	0.01	15047	0.917	73.2	2.5	0.76	14863	1.023

TABLE 2

A-11

Less than 1.5% Ash

DOE SAMP.	COALBED NAME		1.30 FLOAT 3/8" X 100M				1.60 FLOAT CLEAN COAL				ASH FUSION TEMP			
			YIELD	ASH	TOTAL SULFUR	BTU/LB	#S02/ M BTU	MAF F.CARBON	FUEL RATIO	HGI	FSI	SOFT	DEFORM	FLUID
1	2	5	21	22	23	24	25	26	27	28	29	30	31	32
273	MID. KITT		64.6	2.0	0.69	14755	0.935	61.3	1.58	62	7.5	2910	-	-
290	MID. KITT		83.1	1.9	0.48	14475	0.663	58.3	1.40	47	4.5	2910	-	-
301	LOW. KITT		85.4	1.5	0.65	14571	0.892	59.4	1.46	52	5.0	-	-	-
303	LOW. KITT		87.4	1.5	0.64	14588	0.877	60.2	1.51	56	7.0	2370	2450	2670
327	LOW. KITT		38.6	1.7	0.74	15394	0.961	86.4	6.35	-	9.0	2910	-	-
370	BROOKVILLE		66.5	1.5	0.85	15115	1.125	53.1	1.13	-	-	-	-	-
373	BROOKVILLE		86.2	1.7	0.70	14536	0.963	59.8	1.49	-	5.5	2560	2610	2680
374	BROOKVILLE		56.1	2.0	0.67	15239	0.879	74.3	2.89	-	9.0	2910	-	-
394	JELLICO		88.0	1.5	0.79	14543	1.086	60.3	1.52	39	3.5	2090	2140	2250
396	TAGGART		70.6	1.8	0.71	14736	0.964	63.9	1.77	48	5.5	2480	2580	2780
398	IMBODEN		81.4	1.5	0.88	14982	1.175	65.7	1.92	53	9.0	2780	2830	2880
399	DORCHESTER		95.0	1.1	0.85	14960	1.136	63.7	1.75	55	9.0	2030	2080	2130
410	BLACK CREEK		82.6	1.4	0.71	15349	0.925	65.8	1.92	-	-	-	-	-
413	BLACK CREEK		88.1	1.1	0.61	15291	0.798	68.0	2.13	66	9.0	2910	-	-
414	BLACK CREEK		92.9	1.2	0.63	14881	0.847	61.3	1.58	41	7.0	2910	-	-
559	SECOR		94.7	1.7	0.58	14837	0.782	63.8	1.76	45	6.5	2090	2220	2360
727	COAL BASIN D		85.0	1.7	0.51	14046	0.726	57.8	1.37	53	1.5	-	2800	5
729	COAL BASIN E		85.3	2.2	0.34	14026	0.485	58.6	1.42	43	1.5	2370	2420	2520
841	NO. 6		40.2	1.7	1.23	13992	1.758	58.6	1.42	-	-	-	-	-
843	NO. 6		60.6	1.6	0.92	14027	1.312	55.7	1.26	-	-	-	-	-
853	HAZARD 5A		93.9	1.4	0.56	14455	0.775	60.7	1.54	43	2.0	2840	2910	-
860	UPPER ELKHORN #		72.9	1.7	0.90	14563	1.236	60.4	1.53	41	4.5	2250	2300	2360
861	UPPER ELKHORN #		90.6	1.2	0.48	14485	0.663	59.9	1.49	38	1.5	2720	2770	2820
862	UPPER ELKHORN #		71.5	1.4	0.79	14540	1.087	61.6	1.60	39	3.0	2620	2680	2780
863	UPPER ELKHORN #		86.4	1.6	0.79	14668	1.077	57.5	1.35	46	5.0	2910	-	-
864	UPPER ELKHORN #		80.7	1.8	0.78	14797	1.054	59.0	1.44	45	5.0	2680	2730	2780
873	WINIFREDE		69.7	1.7	0.72	14673	0.981	59.8	1.49	37	4.0	2910	-	-
874	CHILTON		76.8	1.9	0.66	14907	0.885	64.7	1.83	-	8.5	2910	-	-
877	NO. 2 GAS		75.6	1.5	0.89	14702	1.211	58.1	1.39	39	5.5	2530	2580	2630
878	POWELTON		66.4	1.7	0.70	14986	0.934	67.0	2.03	-	9.0	2910	-	-

TABLE 3

A-12

Less than 2100°F Ash Softening Temperature

DOE SAMP.	CROSS REF	COUNTY	STATE	COALBED NAME	NO.	ESTIMATED RESERVES COUNTY STATE (MILLIONS OF TONS		SAMPLE CONFORM %	YIELD	ASH
1	2	3	4	5	6	7	8	9A	9	10
W-00399	B322	WISE	VIRGINIA	DORCHESTER	185	79.99	94.22	100.0	92.0	0.8
W-00544	W6	OKMULGEE	OKLAHOMA	CROWEBURG	496	119.79	186.86	16.7	71.4	2.4
* W-00562	B34	MONROE	IOWA	L.COAL FORD	530	509.67	1477.97	20.0	3.5	2.9
* W-00614	W82	CARBON	MONTANA	BROPHY 2	40	N/L	N/L	50.0	5.2	6.3
W-00616	W124	RIO BLANCA	COLORADO	F MOFFAT	152	66.89	66.89	100.0	68.1	3.2
W-00622	W135	ROUTT	COLORADO	NO.4 U.WILLIAMS	169	N/L	1661.05	33.3	16.2	2.8
W-00623	W136	ROUTT	COLORADO	NO.3 U.WILLIAMS	169	N/L	1661.05	33.3	14.5	3.4
W-00639	B340	CARBON	WYOMING	NO. 80	399	N/L	N/L	100.0	3.4	3.2
W-00677	W91	BIG HORN	MONTANA	ANDER/DIETZ 2	520	N/L	N/L	50.0	42.3	3.6
W-00679	W157	BIG HORN	MONTANA	LOWER/DIETZ	520	N/L	N/L	50.0	62.4	3.3
W-00684	W81	POWDER RIVER	MONTANA	SAWYER	524	N/L	N/L	100.0	20.0	4.4
W-00708	W53	SHERIDAN	WYOMING	MONARCH	695	1.11	14.68	100.0	72.5	3.6
W-00709	W54	SHERIDAN	WYOMING	DIETZ #3	697	267.34	902.27	100.0	43.0	4.4
W-00756	B252	SWEETWATER	WYOMING	ROCK SPRINGS #9	793	N/L	N/L	100.0	71.3	1.3
W-00780	W78	CARBON	WYOMING	HANNA 5	819	N/L	N/L	20.0	47.8	3.3
W-00792	W150	CARBON	UTAH	A HIAWATHA	846	N/L	N/L	14.3	76.8	2.0
W-00800	B242	EMERY	UTAH	BLIND CANYON	855	N/L	N/L	100.0	86.4	2.2
W-00804	W153	BIG HORN	MONTANA	ANDER/DIETZ	927	N/L	N/L	40.0	27.6	4.3
W-00806	W155	BIG HORN	MONTANA	ANDER/DIETZ	927	N/L	N/L	40.0	26.0	5.1
* W-00925	B626	LEWIS	W.VIRGINIA	PITTSBURGH	36	254.05	7127.29	2.6	54.1	3.5
W-00967	B625	BARBOUR	W.VIRGINIA	L.KITTANNING	84	N/L	2125.21	25.0	55.4	2.9

TABLE 3 (Continued)

A-13

Less than 2100°F Ash Softening Temperature

DOE SAMP.	COALBED NAME	1.30 FLOAT 14M X 100M						1.40 FLOAT 14M X 100M				
		YIELD	ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%
1	5	9	10	11	12	13	14	15	16	17	18	19
W-00399	DORCHESTER	92.0	0.8	0.82	0.09	15058	0.545	97.9	1.0	0.82	15025	0.546
W-00544	CROWEBURG	71.4	2.4	1.10	0.28	14623	0.752	91.1	3.2	1.27	14494	0.876
* W-00562	L.COAL FORD	3.5	2.9	1.97	0.21	13715	1.436	70.9	4.8	0.64	13404	0.477
* W-00614	BROPHY 2	5.2	6.3	0.87	0.30	12858	0.677	71.4	5.8	1.06	12931	0.820
W-00616	F MOFFAT	68.1	3.2	0.32	0.09	13122	0.244	96.6	3.7	0.33	13054	0.253
W-00622	NO.4 U.WILLIAMS	16.2	2.8	0.49	0.03	12905	0.380	94.2	3.0	0.47	12873	0.365
W-00623	NO.3 U.WILLIAMS	14.5	3.4	0.73	0.09	12932	0.564	94.1	4.8	0.76	12746	0.596
W-00639	NO. 80	3.4	3.2	0.78	0.13	12527	0.623	92.7	4.5	1.05	12327	0.852
W-00677	ANDER/DIETZ 2	42.3	3.6	0.33	0.03	12769	0.258	94.7	3.8	0.30	12740	0.235
W-00679	LOWER/DIETZ	62.4	3.3	0.46	0.05	12947	0.355	97.0	3.5	0.45	12918	0.348
W-00684	SAWYER	20.0	4.4	0.58	0.02	11867	0.489	89.0	5.0	0.60	11787	0.509
W-00708	MONARCH	72.5	3.6	0.49	0.03	12606	0.389	97.0	4.0	0.53	12551	0.422
W-00709	DIETZ #3	43.0	4.4	0.69	0.13	12428	0.555	92.6	5.1	0.80	12329	0.649
W-00756	ROCK SPRINGS #9	71.3	1.3	1.03	0.23	12851	0.802	94.6	1.3	1.05	12851	0.817
W-00780	HANNA 5	47.8	3.3	0.42	0.06	13629	0.308	94.9	4.0	0.42	13467	0.312
W-00792	A HIAWATHA	76.8	2.0	0.56	0.07	14331	0.391	90.8	2.7	0.56	14216	0.394
W-00800	BLIND CANYON	86.4	2.2	0.48	0.04	14261	0.337	93.1	2.7	0.49	14170	0.346
W-00804	ANDER/DIETZ	27.6	4.3	0.25	0.02	12421	0.201	92.2	4.3	0.26	12421	0.209
W-00806	ANDER/DIETZ	26.0	5.1	0.93	0.18	12542	0.741	83.8	5.6	1.08	12471	0.866
* W-00925	PITTSBURGH	54.1	3.5	1.39	0.53	14243	0.976	90.0	4.7	0.69	14051	0.491
W-00967	L.KITTANNING	55.4	2.9	0.72	0.11	15120	0.476	72.5	4.6	0.76	14830	0.512

TABLE 3 (Continued)

A-14

Less than 2100°F Ash Softening Temperature

1.60 FLOAT 14M X 100M

DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%	ASH FUSION HGI SOFT	MF VOLATILES	
1	5	20	21	22	23	24	27	29	32
W-00399	DORCHESTER	98.6	1.0	0.83	15025	0.552	55	2080	35.9
W-00544	CROWEBURG	95.6	3.7	1.38	14413	0.957	-	1980	37.7
* W-00562	L.COAL FORD	84.3	7.4	2.56	12978	1.973	-	1940	43.2
* W-00614	BROPHY 2	89.0	7.9	1.36	12625	1.077	44	2060	41.2
W-00616	F MOFFAT	98.6	4.0	0.34	13012	0.261	42	2100	39.3
W-00622	NO.4 U.WILLIAMS	96.3	3.4	0.46	12810	0.359	41	2000	39.7
W-00623	NO.3 U.WILLIAMS	98.0	4.9	0.76	12733	0.597	35	2080	40.6
W-00639	NO. 80	98.1	5.2	1.10	12219	0.900	44	2090	41.3
W-00677	ANDER/DIETZ 2	98.6	4.0	0.30	12712	0.236	45	2070	41.8
W-00679	LOWER/DIETZ	99.0	3.6	0.46	12903	0.357	40	2040	44.6
W-00684	SAWYER	97.4	5.6	0.61	11708	0.521	37	2100	42.2
W-00708	MONARCH	99.1	4.3	0.54	12510	0.432	28	2070	44.1
W-00709	DIETZ #3	97.0	5.7	0.93	12243	0.760	34	2100	42.9
W-00756	ROCK SPRINGS #9	98.6	1.6	1.10	12808	0.859	50	2080	45.4
W-00780	HANNA 5	96.5	4.3	0.43	13397	0.321	35	2070	46.1
W-00792	A HIAWATHA	92.9	3.1	0.57	14150	0.403	48	2100	45.2
W-00800	BLIND CANYON	95.9	3.2	0.50	14080	0.355	45	2070	45.7
W-00804	ANDER/DIETZ	97.8	4.6	0.26	12379	0.210	39	2040	43.6
W-00806	ANDER/DIETZ	93.0	6.4	1.14	12357	0.923	43	2040	44.7
* W-00925	PITTSBURGH	95.7	5.4	1.72	13940	1.234	-	2090	41.2
W-00967	L.KITTANNING	82.9	7.1	0.80	14405	0.555	-	291	33.0

TABLE 4

A-15

2101-2400°F Ash Softening Temperature

DOE SAMP.	CROSS REF	COUNTY	STATE	COALBED NAME	NO.	ESTIMATED RESERVES			YIELD	ASH
						COUNTY	STATE	SAMPLE		
						(MILLIONS OF	TONS	CONFORM.		
1	2	3	4	5	6	7	8	8A	9	10
* W-00090	B407	JEFFERSON	Ohio	PITTSBURGH	36	632.47	4612.50	2.7	44.9	2.9
W-00153	B137	GARRETT	Maryland	LOWER BAKERSTOWN	63	152.18	237.49	50.0	13.5	1.7
W-00155	B397	SOMERSET	Pennsylvania	LOWER BAKERSTOWN	63	N/L	N/L	66.7	61.7	2.7
* W-00156	B461	SOMERSET	Pennsylvania	LOWER BAKERSTOWN	63	N/L	N/L	66.7	44.1	2.8
W-00158	B526	WESTMORELAND	Pennsylvania	BRUSH CREEK	67	N/L	4.88	100.0	67.5	2.4
* W-00172	B575	MUSKINGUM	Ohio	UPPER FREEPORT #7	71	122.86	3030.33	25.0	51.8	2.9
* W-00188	B162	ARMSTRONG	Pennsylvania	UPPER FREEPORT	71	396.90	4587.35	66.7	64.9	2.3
W-00200	B473	JEFFERSON	Pennsylvania	UPPER FREEPORT	71	15.85	4587.35	66.7	73.7	2.1
W-00223	B403	ARMSTRONG	Pennsylvania	LOWER FREEPORT	74	193.58	2251.02	4.8	43.9	3.0
W-00239	B175	CLEARFIELD	Pennsylvania	UPPER KITTANNING	76	140.75	1066.39	8.3	23.0	3.2
W-00265	B460	COLUMBIANA	Ohio	MIDDLE KITTANNING	80	46.84	5797.78	3.6	59.5	1.6
* W-00287	B395	ARMSTRONG	Pennsylvania	MIDDLE KITTANNING	80	7.48	826.41	12.5	55.9	2.5
* W-00289	B414	BUTLER	Pennsylvania	MIDDLE KITTANNING	80	336.62	826.41	12.5	52.0	2.7
W-00328	B 60	CLARION	Pennsylvania	LOWER KITTANNING	84	254.50	3072.08	9.3	57.2	2.3
* W-00335	B120	CLINTON	Pennsylvania	LOWER KITTANNING	84	9.52	3072.08	9.3	62.3	2.1
W-00338	B154	CLEARFIELD	Pennsylvania	LOWER KITTANNING	84	398.67	3072.08	9.3	42.1	2.9
* W-00357	B472	JEFFERSON	Pennsylvania	LOWER KITTANNING	84	170.47	3072.08	9.3	55.6	1.9
W-00394	B324	CAMPBELL	Tennessee	JELICO	151	18.81	51.27	25.0	64.6	1.5
W-00403	B102	DICKENSON	Virginia	UPPER BANNER	214	162.15	242.93	100.0	62.9	2.6
W-00406	B 99	RUSSELL	Virginia	TILLER	269	84.81	166.18	100.0	67.6	2.3
W-00465	B 67	VIGO	Indiana	NO. VII	480	393.20	1509.18	33.3	37.7	2.6
* W-00491	B203	DOUGLAS	Illinois	NO. 6	484	390.61	35615.77	7.1	34.3	3.0
* W-00495	B209	WILLIAMSON	Illinois	NO. 6	484	665.29	35615.77	7.1	44.0	2.7
W-00545	W 8	ROGERS	Oklahoma	CROWEBURG	496	119.79	186.86	66.7	75.3	2.7
W-00546	W 7	WAGONER	Oklahoma	CROWEBURG	496	?	186.86	66.7	84.2	2.8
W-00559	W 9	WAGONER	Oklahoma	SECOR	527	N/L	57.92	100.0	88.8	1.4
* W-00578	W 1	LOGAN	Arkansas	PARIS	551	10.10	15.00	100.0	73.9	4.1
W-00582	W 3	FRANKLIN	Arkansas	CHARLESTON	554	13.10	42.10	66.7	42.0	3.4
W-00583	B495	JOHNSON	Arkansas	CHARLESTON	554	20.00	42.10	66.7	10.2	2.1
W-00589	B505	SEBASTIAN	Arkansas	UPPER HART SHORNE	562	4.50	4.50	33.3	56.0	2.4
W-00594	B506	POPE	Arkansas	UNCORRELATED	799	---	---	---	8.0	4.2
W-00595	B 31	MAHASKA	Iowa	UNCORRELATED	799	---	---	---	8.9	1.1
W-00618	W121	MOFFAT	Colorado	H	154	81.88	252.52	100.0	15.9	4.2
W-00619	W134	MOFFAT	Colorado	P SEAM-WILLIAMS FOR	160	N/L	46.97	100.0	14.4	2.6
W-00620	W120	MOFFAT	Colorado	B	161	4.85	6.23	100.0	32.6	3.4
W-00621	W122	MOFFAT	Colorado	R RIDER	162	2.72	2.72	100.0	43.0	3.6
W-00624	W137	ROUTT	Colorado	2 UPPER WILLIAMS F	169	N/L	183.08	50.0	6.6	3.0
W-00625	W138	ROUTT	Colorado	#1 SEAM(UPPER WILLI	169	N/L	183.08	50.0	34.9	4.0
W-00626	W139	ROUTT	Colorado	#5 SEAM(U.WILLIAMS	169	N/L	183.08	50.0	5.1	3.8
W-00628	W 66	CARBON	Wyoming	BED 78 BOTTOM	178	N/L	N/L	100.0	60.4	3.0
W-00629	W 67	CARBON	Wyoming	BED 78 TOP	178	N/L	N/L	100.0	43.2	4.2
W-00631	W 14	MCKINLEY	New Mexico	DILCO	279	N/L	N/L	66.7	70.8	4.1
W-00632	W 16	MCKINLEY	New Mexico	DILCO	279	N/L	N/L	66.7	70.0	4.8
W-00636	W 72	CARBON	Wyoming	63 BED	394	N/L	N/L	100.0	9.3	4.5
W-00638	W 63	CARBON	Wyoming	BED 65	398	N/L	N/L	50.0	11.4	2.3
W-00640	B341	CARBON	Wyoming	NO. 82	401	N/L	N/L	100.0	13.0	2.9
W-00648	W 65	CARBON	Wyoming	BED 25	425	N/L	N/L	100.0	1.6	3.6

2101-2400°F Ash Softening Temperature

DOE SAMP.	CROSS REF	COUNTY	STATE	COALBED NAME	NO.	COUNTY	ESTIMATED RESERVES STATE (MILLIONS OF TONS)	SAMPLE CONFORM %	YIELD	ASH
1	2	3	4	5	6	7	8	8A	9	10
W-00651	W 64	CARBON	Wyoming	BED 51	451	N/L	N/L	100.0	14.4	5.3
W-00655	B262	MCKINLEY	New Mexico	BLUE	479	N/L	N/L	66.7	44.8	2.9
W-00657	B328	MCKINLEY	New Mexico	BLUE	479	N/L	N/L	66.7	66.9	2.6
W-00665	W 74	SWEETWATER	Wyoming	DEADMAN UPPER	495	N/L	N/L	100.0	3.9	4.1
W-00666	W 73	SWEETWATER	Wyoming	LOWER DEADMAN	496	N/L	N/L	100.0	39.8	4.5
W-00676	W123	MOFFAT	Colorado	I	515	N/L	N/L	100.0	22.0	3.3
W-00678	W156	BIG HORN	Montana	(A) DI LOWER DIETZ	520	N/L	N/L	25.0	76.6	3.0
W-00685	B290	ROSEBUD	Montana	MCKAY	525	N/L	N/L	100.0	26.3	3.3
W-00686	W 75	SWEETWATER	Wyoming	C	533	N/L	N/L	100.0	30.2	2.9
W-00704	W 84	BIG HORN	Montana	ROBINSON	571	N/L	N/L	100.0	17.4	4.8
W-00710	W 50	CAMPBELL	Wyoming	WYODAK-ANDERSON	699	1174.35	1634.37	50.0	90.5	5.4
W-00713	W 60	CAMPBELL	Wyoming	WYODAK	699	1174.35	1634.37	50.0	93.3	4.9
W-00716	W130	PITKIN	Colorado	DUTCH	702	N/L	N/L	100.0	80.1	2.3
W-00718	W127	PITKIN	Colorado	B CARBONDALE	705	N/L	N/L	50.0	79.8	2.6
W-00721	W128	PITKIN	Colorado	ANDERSON	718	16.44	26.96	100.0	65.7	3.1
W-00730	W129	MOFFAT	Colorado	F	757	N/L	77.74	100.0	14.6	2.5
W-00737	B295	WELD	Colorado	LARAMIE NO. 3	768	294.36	302.41	100.0	10.1	3.7
W-00739	W141	MOFFAT	Colorado	X SEAM	775	N/L	N/L	100.0	20.6	2.5
W-00740	W 96	LINCOLN	Wyoming	ADAVILLE #8 BOTTOM	778	N/L	N/L	100.0	56.1	2.5
W-00741	W 97	LINCOLN	Wyoming	ADAVILLE #4	778	N/L	N/L	100.0	73.3	2.6
W-00742	W 98	LINCOLN	Wyoming	ADAVILLE #2	778	N/L	N/L	100.0	79.2	2.6
W-00745	W105	LINCOLN	Wyoming	ADAVILLE #7 UPPER	778	N/L	N/L	100.0	68.8	3.2
W-00746	W 99	LINCOLN	Wyoming	ADAVILLE #1	781	N/L	N/L	75.0	68.8	2.4
W-00747	W100	LINCOLN	Wyoming	ADAVILLE #1	781	N/L	N/L	75.0	64.2	2.5
W-00748	W101	LINCOLN	Wyoming	ADAVILLE #1	781	N/L	N/L	75.0	60.0	2.8
W-00750	W 95	LINCOLN	Wyoming	ADAVILLE	782	N/L	N/L	100.0	74.6	3.3
W-00751	B408	LINCOLN	Wyoming	ADAVILLE #6 (TOP BE	782	N/L	N/L	100.0	26.4	3.0
W-00752	B409	LINCOLN	Wyoming	ADAVILLE NO.6 (BOT.	782	N/L	N/L	100.0	69.9	3.2
W-00754	W 15	MCKINLEY	New Mexico	SUNDANCE (BLACKDIAMOND)	785	N/L	N/L	100.0	70.5	2.7
W-00755	B254	SWEETWATER	Wyoming	ROCK SPRINGS NO. 3	790	N/L	N/L	100.0	60.7	2.0
W-00757	B255	SWEETWATER	Wyoming	ROCK SPRINGS NO. 11	796	N/L	N/L	100.0	69.5	1.8
W-00764	B307	CARBON	Utah	UNCORRELATED	799	---	---	---	68.4	2.9
W-00765	B308	CARBON	Utah	UNCORRELATED	799	---	---	---	89.2	2.1
W-00766	W144	CARBON	Utah	LOWER SUNNYSIDE	802	N/L	N/L	100.0	59.5	1.8
W-00771	B287	ROSEBUD	Montana	ROSEBUD	808	N/L	N/L	80.0	12.6	4.5
W-00772	B288	ROSEBUD	Montana	ROSEBUD	808	N/L	N/L	80.0	15.6	4.7
W-00774	B291	ROSEBUD	Montana	ROSEBUD	808	N/L	N/L	80.0	19.7	4.9
W-00775	B334	ROSEBUD	Montana	ROSEBUD (TOP)	808	N/L	N/L	80.0	50.1	4.6
W-00776	W 76	CARBON	Wyoming	HANNA 2	817	N/L	N/L	100.0	42.5	4.0
W-00777	W 77	CARBON	Wyoming	HANNA 2 MIDDLE	817	N/L	N/L	100.0	46.7	3.9
W-00778	W 68	CARBON	Wyoming	HANNA 5 TOP	819	N/L	N/L	80.0	N/L	80.0
W-00779	W 69	CARBON	Wyoming	HANNA 5 BOTTOM	819	N/L	N/L	80.0	N/L	80.0
W-00781	W 79	CARBON	Wyoming	HANNA 5 (BLOCK 2) #1	819	N/L	N/L	80.0	N/L	80.0
W-00782	W 80	CARBON	Wyoming	HANNA 5 (BLOCK 2) #1	819	N/L	N/L	80.0	N/L	80.0
W-00785	B251	CARBON	Utah	CASTLE GATE A	830	N/L	N/L	100.0	86.7	2.7
W-00786	W145	CARBON	Utah	CASTLE GATE D	836	N/L	N/L	100.0	68.9	3.5
W-00787	W146	CARBON	Utah	SUB 3	844	N/L	N/L	100.0	65.4	3.7

TABLE 4 (Continued)

A-17

2101-2400°F Ash Softening Temperature

DOE SAMP.	CROSS REF	COUNTY	STATE	COALBED NAME	ESTIMATED RESERVES NO. COUNTY STATE (MILLIONS OF TONS)	SAMPLE CONFORM %	YIELD	ASH		
1	2	3	4	5	6	7	8	8A	9	10
W-00788	W148	CARBON	Utah	SUBSEAM #3	844	N/L	N/L	100.0	65.8	2.9
W-00789	B310	CARBON	Utah	SUBSEAM NO. 3	844	N/L	N/L	100.0	72.3	3.0
W-00796	B360	SEVIER	Utah	HIAWATHA	846	N/L	N/L	14.3	35.6	1.8
W-00798	W118	SEVIER	Utah	UPPER HIAWATHA #1	847	N/L	N/L	50.0	39.5	2.4
W-00799	B250	EMERY	Utah	FERRON J	853	N/L	N/L	100.0	44.1	2.3
W-00801	W151	CARBON	Utah	B SEAM (BEAR CANYON	856	N/L	N/L	100.0	78.7	1.8
W-00802	W 89	BIG HORN	Montana	ANDERSON DIETZ I	927	N/L	N/L	60.0	69.6	2.7
W-00803	W 90	BIG HORN	Montana	ANDERSON DIETZ I	927	N/L	N/L	60.0	76.6	3.3
W-00805	W154	BIG HORN	Montana	ANDERSON DIETZ	927	N/L	N/L	60.0	81.5	3.7
W-00808	W 92	BIG HORN	Montana	DIETZ 1&2	935	N/L	N/L	100.0	63.4	3.2
W-00809	W 93	BIG HORN	Montana	DIETZ 1&2	935	N/L	N/L	100.0	46.8	3.7
W-00844	B367	OHIO	Kentucky (WEST)	NO. 6	506	13.99	506.38	33.3	60.9	1.6
W-00847	B536	ELLIOTT	Kentucky (EAST)	PRINCESS NO. 7	77	N/L	138.02	100.0	68.2	2.3
W-00860	B303	MCCREARY	Kentucky (EAST)	UPPER ELKHORN NO. 3	151	0.40	2059.31	50.0	66.7	1.3
W-00887	B600	LEWIS	West Virginia	REDSTONE	33	268.15	448.27	11.1	57.9	3.4
* W-00907	B 85	HARRISON	West Virginia	PITTSBURGH	36	386.14	7192.99	10.5	63.5	3.8
* W-00914	B601	GILMER	West Virginia	PITTSBURGH	36	169.48	7192.99	10.5	61.1	3.5
* W-00915	B602	LEWIS	West Virginia	PITTSBURGH	36	278.45	7192.99	10.5	58.8	3.1
* W-00918	B610	BARBOUR	West Virginia	PITTSBURGH	36	132.87	7192.99	10.5	71.4	3.6
W-00971	B650	UPSHUR	West Virginia	LOWER KITTANNING	84	N/L	2274.70	12.5	15.8	3.9

TABLE 4 (Continued)

A-18

2101-2400°F Ash Softening Temperature

DOE SAMP.	COALBED NAME	YIELD	1.30 FLOAT 14M X 100M					1.40 FLOAT 14M X 100M				
			ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%
1	5	9	10	11	12	13	14	15	16	17	18	19
* W-00090	PITTSBURGH	44.9	2.9	1.33	0.38	14463	0.920	78.7	4.7	1.58	14172	1.115
W-00153	LOWER BAKERSTOW	13.5	1.7	0.70	0.12	15464	0.453	62.5	4.3	1.05	15013	0.699
W-00155	LOWER BAKERSTOW	61.7	2.7	1.16	0.27	15349	0.756	84.2	3.7	1.33	15179	0.876
* W-00156	LOWER BAKERSTOW	44.1	2.8	1.38	0.57	15251	0.905	84.6	4.4	1.51	14979	1.008
W-00158	BRUSH CREEK	67.5	2.4	0.99	0.26	15214	0.651	87.9	3.9	1.07	14962	0.715
* W-00172	UPPER FREEPORT	51.8	2.9	1.27	0.29	14175	0.896	76.5	4.1	1.59	13984	1.137
* W-00188	UPPER FREEPORT	64.9	2.3	1.28	0.24	14863	0.861	82.3	3.4	1.60	14688	1.089
W-00200	UPPER FREEPORT	73.7	2.1	1.16	0.21	14986	0.774	86.8	3.0	1.19	14841	0.802
W-00223	LOWER FREEPORT	43.9	3.0	1.25	0.48	14877	0.840	76.8	5.3	1.44	14486	0.994
W-00239	UPPER KITTANNIN	23.0	3.2	0.45	0.03	14412	0.312	71.0	4.4	0.43	14206	0.303
W-00265	MIDDLE KITTANNI	59.5	1.6	0.86	0.19	14828	0.580	76.5	2.8	1.02	14616	0.698
* W-00287	MIDDLE KITTANNI	55.9	2.5	1.59	0.43	14956	1.063	74.3	3.9	1.73	14727	1.175
* W-00289	MIDDLE KITTANNI	52.0	2.7	1.42	0.41	14866	0.955	78.4	4.4	1.70	14561	1.168
W-00328	LOWER KITTANNIN	57.2	2.3	1.20	0.30	14702	0.816	80.9	4.1	1.44	14419	0.999
* W-00335	LOWER KITTANNIN	62.3	2.1	1.49	0.33	15320	0.973	78.9	2.8	1.65	15206	1.085
W-00338	LOWER KITTANNIN	42.1	2.9	1.25	0.53	15170	0.824	72.4	4.5	1.60	14907	1.073
* W-00357	LOWER KITTANNIN	55.6	1.9	1.38	0.38	15307	0.902	72.2	3.3	1.64	15074	1.088
W-00394	JELICO	64.6	1.5	0.76	0.10	14615	0.520	96.9	1.7	0.77	14582	0.528
W-00403	UPPER BANNER	62.9	2.6	0.63	0.04	15164	0.415	81.7	3.9	0.66	14950	0.441
W-00406	TILLER	67.6	2.3	0.52	0.01	15137	0.344	80.0	3.0	0.52	15025	0.346
W-00465	NO. VII	37.7	2.6	0.68	0.15	14028	0.485	78.7	5.5	0.73	13604	0.537
* W-00491	NO. 6	34.3	3.0	1.59	0.46	14077	1.130	75.6	3.7	1.56	13967	1.117
* W-00495	NO. 6	44.0	2.7	1.45	0.46	14158	1.024	79.5	4.8	1.60	13833	1.157
W-00545	CROWEBURG	75.3	2.7	0.62	0.04	15074	0.411	90.1	3.3	0.61	14936	0.408
W-00546	CROWEBURG	84.2	2.8	0.49	0.07	15279	0.321	94.2	3.5	0.50	15114	0.331
W-00559	SECOR	88.8	1.4	0.51	0.16	14920	0.342	96.5	1.6	0.56	14890	0.376
* W-00578	PARIS	73.9	4.1	1.52	1.18	15255	0.996	89.2	4.6	1.77	15169	1.167
W-00582	CHARLESTON	42.0	3.4	1.17	0.53	15333	0.763	87.0	4.5	1.33	15141	0.878
W-00583	CHARLESTON	10.2	2.1	0.79	0.23	15452	0.511	92.3	3.3	0.77	15216	0.506
W-00589	UPPER HART SHOR	56.0	2.4	0.83	0.09	15324	0.542	75.6	3.3	0.88	15155	0.581
W-00594	UNCORRELATED	8.0	4.2	0.97	0.20	14738	0.658	61.5	4.9	1.07	14621	0.732
W-00595	UNCORRELATED	8.9	1.1	0.87	0.05	14063	0.619	89.2	3.4	0.94	13785	0.682
W-00618	H	15.9	4.2	0.57	0.06	12787	0.446	86.5	5.2	0.54	12644	0.427
W-00619	P SEAM-WILLIAMS	14.4	2.6	0.32	0.15	13102	0.244	93.7	3.0	0.33	13037	0.253
W-00620	B	32.6	3.4	0.38	0.05	12825	0.296	88.9	3.7	0.35	12779	0.274
W-00621	R RIDER	43.0	3.6	0.69	0.03	12667	0.545	87.8	5.0	0.72	12474	0.577
W-00624	2 (UPPER WILLIA	6.6	3.0	0.34	0.18	13000	0.262	89.2	3.6	0.32	12907	0.248
W-00625	#1 SEAM(UPPER W	34.9	4.0	0.41	0.10	12880	0.318	94.0	4.3	0.45	12836	0.351
W-00626	#5 SEAM(U.WILLI	5.1	3.8	0.37	0.11	12857	0.288	93.9	4.1	0.32	12811	0.250
W-00628	BED 78 BOTTOM	60.4	3.0	0.81	0.14	13331	0.608	94.3	4.3	0.90	13141	0.685
W-00629	BED 78 TOP	43.2	4.2	0.69	0.13	13223	0.522	83.5	5.4	0.81	13040	0.621
W-00631	DILCO	70.8	4.1	0.46	0.04	13524	0.340	92.2	4.9	0.46	13400	0.343
W-00632	DILCO	70.0	4.8	0.56	0.05	13325	0.420	85.1	5.5	0.56	13219	0.424
W-00636	63 BED	9.3	4.5	0.95	0.15	12860	0.739	89.2	5.7	0.97	12669	0.766
W-00638	BED 65	11.4	2.3	0.25	0.17	13061	0.191	91.3	2.7	0.29	12975	0.224
W-00640	NO. 82	13.0	2.9	0.54	0.10	12679	0.426	95.6	3.4	0.56	12579	0.445
W-00648	BED 25	1.6	3.6	0.45	0.14	12648	0.356	78.0	4.7	0.43	12485	0.344

TABLE 4 (Continued)

A-19

2101-2400°F Ash Softening Temperature

1.30 FLOAT 14M X 100M								1.40 FLOAT 14M X 100M				
DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	EXPECT SO ₂ EMMIS 50%	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO ₂ EMMIS 50%
1	5	9	10	11	12	13	14	15	16	17	18	19
W-00651	BED 51	14.4	5.3	0.47	0.10	12655	0.371	78.8	5.9	0.49	12557	0.390
W-00655	BLUE	44.8	2.9	0.47	0.11	13335	0.352	88.8	3.7	0.48	13207	0.363
W-00657	BLUE	66.9	2.6	0.52	0.07	13385	0.388	94.3	3.3	0.51	13298	0.384
W-00665	DEADMAN UPPER	3.9	4.1	0.52	0.06	12569	0.414	81.0	4.5	0.47	12514	0.376
W-00666	LOWER DEADMAN	39.8	4.5	0.65	0.04	12881	0.505	80.5	5.6	0.65	12724	0.511
W-00676	I	22.0	3.3	0.36	0.03	12922	0.279	91.8	4.0	0.39	12822	0.304
W-00678	(A) DI LOWER DI	76.6	3.0	0.24	0.05	12937	0.186	95.7	3.2	0.24	12908	0.186
W-00685	MCKAY	26.3	3.3	0.59	0.06	12179	0.484	74.3	4.1	0.46	12077	0.381
W-00686	C	30.2	2.9	0.38	0.03	12788	0.297	79.8	3.8	0.38	12665	0.300
W-00704	ROBINSON	17.4	4.8	0.45	0.09	12201	0.369	78.4	5.0	0.33	12176	0.271
W-00710	WYODAK-ANDERSON	90.5	5.4	0.55	0.08	12434	0.442	97.5	5.7	0.56	12392	0.452
W-00713	WYODAK	93.3	4.9	0.37	0.06	12253	0.302	99.3	5.0	0.37	12238	0.302
W-00716	DUTCH	80.1	2.3	0.59	0.03	15653	0.377	91.9	2.9	0.59	15529	0.380
W-00718	B CARBONDALE	79.8	2.6	0.55	0.04	15245	0.361	94.1	3.6	0.62	15049	0.412
W-00721	ANDERSON	65.7	3.1	0.48	0.06	15105	0.318	84.7	4.2	0.50	14913	0.335
W-00730	F	14.6	2.5	0.42	0.03	13237	0.317	95.1	3.6	0.44	13075	0.337
W-00737	LARAMIE NO. 3	10.1	3.7	0.39	0.05	12356	0.316	91.0	4.0	0.39	12315	0.317
W-00739	X SEAM	20.6	2.5	0.32	0.02	13180	0.243	92.7	3.0	0.33	13101	0.252
W-00740	ADAVILLE #8 BDT	56.1	2.5	0.38	0.02	12808	0.297	92.7	2.7	0.36	12780	0.282
W-00741	ADAVILLE #4	73.3	2.6	0.29	0.03	12823	0.226	97.8	3.0	0.31	12766	0.243
W-00742	ADAVILLE #2	79.2	2.6	0.31	0.06	13033	0.238	95.9	2.9	0.32	12989	0.246
W-00745	ADAVILLE #7 UPP	68.8	3.2	0.44	0.04	12894	0.341	96.0	3.6	0.44	12839	0.343
W-00746	ADAVILLE #1	68.8	2.4	0.48	0.04	13266	0.362	94.9	2.5	0.48	13250	0.362
W-00747	ADAVILLE #1	64.2	2.5	0.61	0.04	13246	0.461	95.4	2.8	0.72	13203	0.545
W-00748	ADAVILLE #1	60.0	2.8	0.67	0.03	13303	0.504	89.5	3.2	0.73	13242	0.551
W-00750	ADAVILLE	74.6	3.3	0.84	0.05	13214	0.636	95.2	3.8	0.82	13138	0.624
W-00751	ADAVILLE #6 LTD	26.4	3.0	0.58	0.15	11417	0.508	72.5	3.0	0.55	11417	0.482
W-00752	ADAVILLE NO. 6 I	69.9	3.2	0.52	0.13	12182	0.427	93.5	3.3	0.54	12176	0.444
W-00754	SUNDANCE (BLACKD	70.5	2.7	0.74	0.05	13906	0.532	91.5	3.9	0.74	13715	0.540
W-00755	ROCK SPRINGS NO	60.7	2.0	0.82	0.08	13226	0.620	84.8	2.5	0.85	13147	0.647
W-00757	ROCK SPRINGS NO	69.5	1.8	0.80	0.06	13076	0.612	91.1	1.9	0.81	13061	0.620
W-00764	UNCORRELATED	68.4	2.9	0.54	0.09	14109	0.383	89.0	3.6	0.55	13991	0.393
W-00765	UNCORRELATED	89.2	2.1	0.41	0.08	13795	0.297	96.1	2.5	0.41	13720	0.299
W-00766	LOWER SUNNYSIDE	59.5	1.8	0.55	0.04	14649	0.375	86.7	3.4	0.54	14355	0.376
W-00771	ROSEBUD	12.6	4.5	0.62	0.12	12128	0.511	78.2	5.5	0.57	11998	0.475
W-00772	ROSEBUD	15.6	4.7	0.50	0.05	12175	0.411	78.7	4.9	0.53	12149	0.436
W-00774	ROSEBUD	19.7	4.9	0.48	0.08	12056	0.398	75.1	5.6	0.52	11957	0.435
W-00775	ROSEBUD [TOP]	50.1	4.6	0.67	0.07	12111	0.553	78.2	5.0	0.62	12047	0.515
W-00776	HANNA 2	42.5	4.0	0.59	0.09	13247	0.445	80.7	5.7	0.64	12982	0.493
W-00777	HANNA 2 MIDDLE	46.7	3.9	0.34	0.08	13144	0.259	89.8	4.6	0.35	13029	0.269
W-00778	HANNA 5 TOP	N/L	80.0	0.53	0.12	13385	0.396	91.9	4.0	0.55	13258	0.415
W-00779	HANNA 5 BOTTOM	N/L	80.0	0.41	0.07	13352	0.307	91.8	4.5	0.43	13260	0.324
W-00781	HANNA 5 (BLOCK	N/L	80.0	0.33	0.07	13390	0.246	93.6	3.9	0.34	13328	0.255
W-00782	HANNA 5 (BLOCK2)	N/L	80.0	0.57	0.09	13134	0.434	86.5	4.3	0.64	13034	0.491
W-00785	CASTLE GATE A	86.7	2.7	0.41	0.04	13857	0.296	95.1	3.2	0.41	13759	0.298
W-00786	CASTLE GATE D	68.9	3.5	0.48	0.03	14340	0.335	88.5	4.5	0.48	14162	0.339
W-00787	SUB 3	65.4	3.7	0.50	0.06	14617	0.342	89.7	5.0	0.50	14288	0.350

TABLE 4 (Continued)

A-20

2101-2400°F Ash Softening Temperature

DOE SAMP.	COALBED NAME	YIELD	1.30 FLOAT 14M X 100M						1.40 FLOAT 14M X 100M			
			ASH	TOTAL SULFUR	PYRITIC SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO2 EMMIS 50%
1	5	9	10	11	12	13	14	15	16	17	18	19
W-00788	SUBSEAM #3	65.8	2.9	0.67	0.03	14159	0.473	90.0	3.8	0.68	14016	0.485
W-00789	SUBSEAM NO. 3	72.3	3.0	0.46	0.07	14196	0.324	86.5	4.0	0.46	14018	0.328
W-00796	HIAWATHA	35.6	1.8	0.45	0.09	13517	0.333	86.7	2.8	0.43	13337	0.322
W-00798	UPPER HIAWATHA	39.5	2.4	0.35	0.01	13948	0.251	89.1	3.9	0.36	13615	0.264
W-00799	FERRON J	44.1	2.3	0.37	0.01	14124	0.262	85.9	4.0	0.37	13757	0.269
W-00801	B SEAM (BEAR CA	78.7	1.8	0.58	0.06	14666	0.395	90.7	2.6	0.58	14506	0.400
W-00802	ANDERSON DIETZ	69.6	2.7	0.26	0.04	12780	0.203	94.4	3.0	0.27	12736	0.212
W-00803	ANDERSON DIETZ	76.6	3.3	0.41	0.06	12893	0.318	96.1	3.4	0.43	12878	0.334
W-00805	ANDERSON DIETZ	81.5	3.7	0.25	0.06	12427	0.201	96.1	3.9	0.25	12399	0.202
W-00808	DIETZ 1&2	63.4	3.2	0.36	0.04	12844	0.280	96.5	3.6	0.47	12786	0.368
W-00809	DIETZ 1&2	46.8	3.7	0.43	0.07	12881	0.334	94.6	4.4	0.67	12772	0.525
W-00844	NO. 6	60.9	1.6	0.83	0.27	14300	0.580	84.2	2.7	1.06	14133	0.750
W-00847	PRINCESS NO.7	68.2	2.3	0.83	0.30	14320	0.580	81.5	3.0	0.98	14209	0.690
W-00860	UPPER ELKHORN N	66.7	1.3	0.91	0.16	14778	0.616	82.2	2.0	1.04	14664	0.709
W-00887	REDSTONE	57.9	3.4	1.28	0.41	14374	0.891	91.5	5.0	1.57	14110	1.113
* W-00907	PITTSBURGH	63.5	3.8	1.56	0.31	14514	1.075	82.8	4.7	1.63	14388	1.133
* W-00914	PITTSBURGH	61.1	3.5	1.47	0.23	14181	1.037	87.5	5.1	1.66	13886	1.195
* W-00915	PITTSBURGH	58.8	3.1	1.32	0.30	14285	0.924	80.7	3.9	1.41	14180	0.994
* W-00918	PITTSBURGH	71.4	3.6	1.51	0.41	14870	1.015	89.4	4.4	1.70	14743	1.153
W-00971	LOWER KITTANNIN	15.8	3.9	0.81	0.05	14122	0.574	55.4	5.4	0.77	13874	0.555

TABLE 4 (Continued)

A-21

2101-2400°F Ash Softening Temperature

1.60 FLOAT 14M X 100M

DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO ₂ EMMIS 50%	HBI	ASH FUSION SOFT	MF VOLATILES
1	5	20	21	22	23	24	27	29	32
* W-00090	PITTSBURGH	89.9	6.2	1.78	13929	1.278	-	2190	40.1
W-00153	LOWER BAKERSTOW	79.0	6.2	1.30	14683	0.885	-		
W-00155	LOWER BAKERSTOW	89.1	4.3	1.42	15077	0.942	-		
* W-00156	LOWER BAKERSTOW	96.4	5.7	1.63	14758	1.104	-		
W-00158	BRUSH CREEK	93.8	5.1	1.21	14761	0.820	80	2300	31.3
* W-00172	UPPER FREEPORT	85.0	5.3	1.89	13794	1.370	-	2250	44.4
* W-00188	UPPER FREEPORT	90.2	4.3	1.94	14544	1.334	-	2180	39.1
W-00200	UPPER FREEPORT	92.6	4.0	1.27	14679	0.865	57	2360	36.5
W-00223	LOWER FREEPORT	90.3	7.2	1.60	14163	1.130	-	2360	35.6
W-00239	UPPER KITTANNIN	92.1	6.2	0.44	13898	0.317	108		
W-00265	MIDDLE KITTANNI	84.4	3.8	1.28	14439	0.886	-	2200	37.7
* W-00287	MIDDLE KITTANNI	81.9	5.3	1.91	14498	1.317	-	2380	41.8
* W-00289	MIDDLE KITTANNI	89.1	5.9	2.02	14291	1.413	-	2380	41.8
W-00328	LOWER KITTANNIN	90.8	5.9	1.95	14137	1.379	55	2350	39.3
* W-00335	LOWER KITTANNIN	90.7	3.7	1.84	15058	1.222	108		
W-00338	LOWER KITTANNIN	85.1	6.4	2.05	14594	1.405	95		
* W-00357	LOWER KITTANNIN	81.5	4.8	2.02	14824	1.363	68	2290	35.6
W-00394	JELICO	98.0	1.9	0.78	14549	0.536	39	2140	39.0
W-00403	UPPER BANNER	88.4	5.3	0.70	14719	0.476	-	2390	31.7
W-00406	TILLER	91.2	3.9	0.51	14880	0.343	-	2300	31.0
W-00465	NO. VII	89.9	8.0	0.77	13239	0.582	-	2350	43.0
* W-00491	NO. 6	89.7	5.6	1.62	13670	1.185	57	2350	42.2
* W-00495	NO. 6	88.5	6.2	1.67	13617	1.226	54	2280	38.1
W-00545	CROWEBURG	93.5	3.9	0.61	14798	0.412	56	2300	40.6
W-00546	CROWEBURG	97.2	3.9	0.50	15019	0.333	48	2310	35.6
W-00559	SECOR	98.2	1.8	0.61	14859	0.411	45	2220	35.6
* W-00578	PARIS	94.9	5.1	1.97	15083	1.306	-		
W-00582	CHARLESTON	93.7	5.4	1.44	14984	0.961	-		
W-00583	CHARLESTON	99.1	3.8	0.77	15117	0.509	-		
W-00589	UPPER HART SHOR	80.8	3.9	0.94	15043	0.625	-		
W-00594	UNCORRELATED	88.0	8.0	1.34	14101	0.950	94		
W-00595	UNCORRELATED	94.4	4.4	1.00	13664	0.732	-	2350	44.0
W-00618	H	95.6	6.7	0.55	12429	0.443	42	2270	39.4
W-00619	P SEAM-WILLIAMS	97.7	3.3	0.33	12989	0.254	50	2170	39.8
W-00620	Q	94.9	4.8	0.36	12611	0.285	41	2270	40.3
W-00621	R RIDER	97.8	6.7	0.72	12239	0.588	41	2260	38.4
W-00624	2 (UPPER WILLIA	93.7	4.1	0.32	12830	0.249	40	2150	38.7
W-00625	#1 SEAM(UPPER W	98.3	4.6	0.45	12792	0.352	36	2150	40.2
W-00626	#5 SEAM(U.WILLI	98.1	4.4	0.32	12764	0.251	44	2150	39.9
W-00628	BED 78 BOTTOM	99.0	5.1	0.96	13023	0.737	37	2120	43.6
W-00629	BED 78 TOP	88.9	6.5	0.88	12872	0.684	43	2240	42.8
W-00631	DILCO	96.6	5.8	0.46	13262	0.347	34	2190	44.2
W-00632	DILCO	92.2	7.0	0.55	12992	0.423	37	2220	42.3
W-00636	63 BED	95.9	6.3	1.00	12574	0.795	38	2130	40.9
W-00638	BED 65	94.4	2.9	0.29	12932	0.224	35	2230	39.6
W-00640	NO. 82	98.0	3.6	0.56	12539	0.447	49	2230	41.4
W-00648	BED 25	93.2	6.1	0.44	12279	0.358	29	2170	38.3

2101-2400°F Ash Softening Temperature

1.60 FLOAT 14M X 100M

DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO ₂ EMMIS 50%	HGI	ASH FUSION SOFT	MF VOLATILES
1	5	20	21	22	23	24	27	29	32
W-00651	BED 51	91.2	8.3	0.49	12164	0.403	31	2370	39.7
W-00655	BLUE	97.0	4.9	0.49	13016	0.376	49	2300	44.0
W-00657	BLUE	99.3	4.0	0.51	13211	0.386	42	2130	44.6
W-00665	DEADMAN UPPER	93.4	5.8	0.47	12336	0.381	40	2240	39.0
W-00666	LOWER DEADMAN	91.3	7.5	0.65	12454	0.522	41	2350	40.8
W-00676	I	97.5	4.4	0.40	12765	0.313	42	2310	38.4
W-00678	(A) DI LOWER DI	98.8	3.3	0.25	12894	0.194	43	2190	44.2
W-00685	MCKAY	95.2	5.7	0.48	11875	0.404	46	2210	36.7
W-00686	C	94.0	5.4	0.37	12445	0.297	39	2170	38.1
W-00704	ROBINSON	96.6	6.1	0.33	12038	0.274	58	2110	38.2
W-00710	WYODAK-ANDERSON	99.1	5.9	0.57	12364	0.461	26	2160	44.8
W-00713	WYODAK	99.8	5.0	0.38	12238	0.311	39	2360	46.2
W-00716	DUTCH	95.6	3.4	0.59	15425	0.382	95	2300	27.2
W-00718	B CARBONDALE	98.1	4.1	0.66	14951	0.441	88	2250	30.3
W-00721	ANDERSON	92.1	5.6	0.53	14668	0.361	69	2260	33.2
W-00730	F	98.2	3.8	0.44	13046	0.337	50	2350	41.7
W-00737	LARAMIE NO. 3	98.7	4.5	0.39	12245	0.318	46	2130	39.4
W-00739	X SEAM	97.1	3.4	0.33	13038	0.253	48	2200	40.3
W-00740	ADAVILLE #8 BOT	97.1	2.9	0.37	12753	0.290	47	2150	44.9
W-00741	ADAVILLE #4	98.8	3.1	0.32	12752	0.251	55	2200	44.5
W-00742	ADAVILLE #2	98.6	3.0	0.32	12974	0.247	48	2250	44.4
W-00745	ADAVILLE #7 UPP	98.8	3.7	0.45	12825	0.351	49	2290	45.8
W-00746	ADAVILLE #1	97.6	2.6	0.48	13235	0.363	58	2280	46.7
W-00747	ADAVILLE #1	98.0	3.0	0.74	13174	0.562	54	2210	46.4
W-00748	ADAVILLE #1	95.2	3.5	0.74	13195	0.561	47	2290	46.1
W-00750	ADAVILLE	97.0	4.0	0.83	13108	0.633	60	2230	46.7
W-00751	ADAVILLE #6 [TO	93.1	3.9	0.55	11304	0.487	-	2110	48.2
W-00752	ADAVILLE NO.6 [	96.8	3.9	0.55	12135	0.453	-	2170	43.6
W-00754	SUNDANCE(BLACKD	95.9	4.7	0.74	13587	0.545	40	2380	34.9
W-00755	ROCK SPRINGS NO	94.4	3.6	0.98	12973	0.755	44	2130	44.0
W-00757	ROCK SPRINGS NO	94.0	2.2	0.82	13019	0.630	49	2140	44.6
W-00764	UNCORRELATED	92.6	4.3	0.57	13874	0.411	41	2280	45.4
W-00765	UNCORRELATED	97.8	2.7	0.41	13682	0.300	45	2110	44.5
W-00766	LOWER SUNNYSIDE	94.3	4.7	0.53	14116	0.375	49	2270	38.2
W-00771	ROSEBUD	95.9	7.0	0.58	11802	0.491	49	2350	38.2
W-00772	ROSEBUD	95.7	6.2	0.55	11976	0.459	51	2270	38.8
W-00774	ROSEBUD	94.5	7.1	0.52	11746	0.443	49	2380	38.2
W-00775	ROSEBUD [TOP]	94.4	6.3	0.60	11839	0.507	46	2320	39.2
W-00776	HANNA 2	90.7	7.9	0.67	12639	0.530	36	2370	44.0
W-00777	HANNA 2 MIDDLE	94.2	5.3	0.36	12913	0.279	39	2260	44.8
W-00778	HANNA 5 TOP	96.6	5.0	0.58	13077	0.444	44	2220	43.1
W-00779	HANNA 5 BOTTOM	94.6	5.0	0.45	13168	0.342	32	2150	46.5
W-00781	HANNA 5 (BLOCK	96.2	4.2	0.34	13265	0.256	36	2140	44.9
W-00782	HANNA 5(BLOCK2)	94.2	5.6	0.67	12818	0.523	38	2240	43.1
W-00785	CASTLE GATE A	97.0	3.6	0.41	13680	0.300	46	2190	48.1
W-00786	CASTLE GATE D	92.5	5.1	0.47	14055	0.334	45	2250	44.5
W-00787	SUB 3	95.4	5.7	0.49	14112	0.347	41	2160	45.3

TABLE 4 (Continued)

2101-2400°F Ash Softening Temperature

1.60 FLOAT 14M X 100M

DOE SAMP.	COALBED NAME	YIELD	ASH	TOTAL SULFUR	BTU/LB	EXPECT SO ₂ EMMIS 50%	HGI	ASH FUSION SOFT	MF VOLATILES
1	5	20	21	22	23	24	27	29	32
W-00788	SUBSEAM #3	94.5	4.4	0.70	13920	0.503	48	2310	45.1
W-00789	SUBSEAM NO. 3	90.8	4.9	0.45	13858	0.325	42	2310	44.2
W-00796	HIAWATHA	94.1	3.7	0.44	13175	0.334	-	2140	41.8
W-00798	UPPER HIAWATHA	95.4	4.6	0.35	13459	0.260	44	2110	42.4
W-00799	FERRON J	96.7	5.2	0.37	13498	0.274	39	2190	39.9
W-00801	B SEAM (BEAR CA	95.8	3.7	0.58	14287	0.406	48	2180	44.8
W-00802	ANDERSON DIETZ	98.6	3.1	0.28	12722	0.220	50	2300	42.5
W-00803	ANDERSON DIETZ	98.9	3.5	0.43	12863	0.334	43	2300	44.2
W-00805	ANDERSON DIETZ	98.9	4.0	0.25	12385	0.202	42	2150	44.1
W-00808	DIETZ 1&2	98.9	3.8	0.49	12757	0.384	37	2190	43.7
W-00809	DIETZ 1&2	99.0	4.7	0.69	12726	0.542	45	2130	43.3
W-00844	NO. 6	95.0	4.0	1.33	13935	0.954	-	2190	40.7
W-00847	PRINCESS NO.7	87.3	3.8	1.26	14083	0.895	49	2190	42.6
W-00860	UPPER ELKHORN N	88.4	2.8	1.12	14534	0.771	41	2300	38.5
W-00887	REDSTONE	94.7	5.3	1.73	14060	1.230	-	2120	42.4
* W-00907	PITTSBURGH	91.7	5.8	2.05	14234	1.440	-	2180	43.2
* W-00914	PITTSBURGH	93.0	5.8	1.84	13757	1.337	-	2140	43.9
* W-00915	PITTSBURGH	85.4	4.5	1.61	14101	1.142	-	2310	42.3
* W-00918	PITTSBURGH	93.3	4.8	1.92	14679	1.308	-	2350	40.3
W-00971	LOWER KITTANNIN	77.2	8.7	0.73	13327	0.548	55	2390	29.0

END

**DATE
FILMED**

1 / 28 / 93