THE ROLES OF SLIP GEOMETRY AND HARDENING BEHAVIOUR
IN INTERGRANULAR TOUGHNESS

Progress Report

for the period January 14, 1991 through January 15, 1992

C. Laird / J. Bassani

University of Pennsylvania
Materials Science & Engineering
Mechanical Engineering
Philadelphia, Pennsylvania 19104

November 1991

Prepared for:

THE UNITED STATES DEPARTMENT OF ENERGY

AGREEMENT NO.: DE-FG02-85ER-45188

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DOE Annual Report

In the experimental part of the program, we have made major progress in: 1) understanding the cyclic response of polycrystalline behavior, both from microstructural and cyclic history points of view; 2) relating monocrystalline and polycrystalline behavior; and 3) reconciling apparently conflicting results of different workers. In the theoretical part of the program we have studied strain localization phenomena and, for the first time, have predicted coarse slip bands that develop in the early stages of deformation.

Last year, we believed that copper of different grain size produced a common cyclic stress strain curve at low amplitudes, but that in the strain regime where persistent slip bands (PSB's) form, the flow stress of the large grain sized material was greatest. We attributed this effect to more multislip behavior in the beginning part of the test, which enhanced hardening in the large grain material. We also suspected that there might be texture effects concomitant with the production of different grain sizes which could overlay and confuse the grain size effect. We therefore made a systematic attempt to measure and control both texture and cyclic history. The latter was treated in terms of ramp loading gradually at the start of cycling so as to encourage single slip behavior and suppress multislip. Many more tests have been completed, and those have been supported by extensive TEM studies.

Examples of developments in understanding are offered as follows: 1) We have had to revise our cyclic stress-strain curve upwards (i.e., increased stress) at low amplitudes because we have found that more cycles are needed to reach saturation at these levels than we had previously believed. A minimum of 20,000 cycles is required for saturation. These results are shown in Figure 1 (see the caption for the cyclic histories of the specimens). TEM observations show that the dislocation density gradually increases with accumulation of cycles until a "standard" structure

has been obtained. 2) The cyclic stress-strain curves for large-grained samples have had to be revised downwards. Again, this behavior has been found to be associated with the definition of saturation. If cycling is extended long enough, large-grained specimens undergo cyclic softening until the flow stress decreases to that developed much more quickly in small-grained specimens (see Fig. 2). The behavior of large grained crystals is akin to that of single crystals with "symmetrical" orientations ([100], [100] or [011]), which also undergo cyclic softening. We explain the early hardening by homogeneous deformation involving multi-slip. With extended cycling, a single slip system becomes dominant and the diverse population of Burgers vectors finally encourages slip localization and softening (akin to PSB behavior). This condition is achieved more quickly in small-grained specimens.

These experiments have been helpful in supporting our theoretical studies where multislip is shown to be essential for slip localization.

The successful prediction of coarse slip bands that develop in the early stages of deformation hinged on the detailed description of multislip hardening that had been developed in earlier years under DOE support. To briefly review earlier findings, we found that to reasonably describe: i) the three stages of hardening typically found in uniaxial loading of metal crystals, ii) the dependence of hardening on the orientation of the stress axis with respect to the crystal axis, iii) the reported secondary slips before overshoot - at least in many FCC metals, and iv) details of latent hardening, that the traditional description of hardening had to be significantly altered (Wu, Bassani and Laird; Bassani and Wu, *PRSL* Oct. 1991).

Now we have shown that these aspects of hardening strongly influence strain localization. Coarse slip bands in the early stages of deformation are observed in a wide range of materials when, at initiation, $\epsilon \sim 0.01$ and $(h/\sigma)_{cr} \sim 0.5$, while macroscopic shear bands are observed in the latter stages of deformation where $\epsilon \sim 0.2$ and $(h/\sigma)_{cr} \sim 0.03$. We have been able to predict coarse slip band initiation in

"single-slip" orientations which, until now, had been unexplained except by invoking non-Schmid effects (Asaro and Rice, *JMPS* 25 309, 1977 and Asaro, *Adv. Appl. Mech.* 23 1, 1983, Qin and Bassani, *JMPS*, 1991). The very fine secondary slips alluded to in iii) above provide the key. Furthermore, the details of macroscopic shear bands are also sensitive to secondary slips. For example, in a double slip orientation it turns out to be insufficient to only consider the two primary slip systems in a full three-dimensional analysis as Pierce (*JMPS* 31 133, 1991) did. We also believe that slip interactions are generally important in fine-scaled multi-phase materials, both in issues such as precipitate hardening and their effect on strain localization. Selected results are briefly summarized below.

A simplified analysis of coarse slip bands and macroscopic shear bands using a planar double slip model with the hardening law $h_{ab} = h \begin{bmatrix} 1 & 0 \\ 0 & p \end{bmatrix}$ reveals the importance of fine secondary slips. Figure 3a is a plot of h/σ versus the band angle for various p , where the maximum of each curve corresponds to the first or critical bifurcation, and Fig. 3b $(h/\sigma)_{cr}$ versus p , where Asaro's symmetric double-slip result corresponds to $p=1$ with $(h/\sigma)_{cr}=0.065$. With $p=h_2/h_1(=\dot{\gamma}_1/\dot{\gamma}_2$ at localization, i.e. bifurcation), even in essentially "single slip", i.e. $p \gg 1$, the hardening need not go to zero due to the effects of the fine secondary slip to get slip localizations which are essentially oriented on the slip systems. For example, with $\dot{\gamma}_1 = 10^2 \dot{\gamma}_2$ that $(h/\sigma)_{cr}=0.015$ (Qin and Bassani, 1991).

Using our complete hardening model (Wu, Bassani and Laird; Bassani and Wu, *PRSL* Oct. 1991) for a 3-D crystal in uniaxial tension we predict coarse slip bands at strains on the order of 0.005-0.01 in single slip orientations (see Fig. 4) and macroscopic shear bands at strains on the order of 0.1 (Fig. 5) in symmetric orientations (Mohan and Bassani, 1991). The terminus of each τ - ϵ curve in Figs. 4 and 5, where τ corresponds to the uniaxial Kirchhoff stress and ϵ the logarithmic

strain, is the point where the shear band initiates (bifurcation). Consistent with experimental observations, i) the coarse slip bands are predicted at $(h/\sigma)_{cr} \sim O(1)$ and are aligned with the primary slip system and ii) the macroscopic shear bands are predicted at $(h/\sigma)_{cr} \sim 0.035$ and are at a misorientation from the primary slip system, whereas the analyses of Pierce (*JMPS* 31 133, 1991) which neglected the fine secondary slips predicted a much lower level of hardening and no misorientation.

Fig. 1 Cyclic stress strain curves for polycrystalline copper of small grain size: ANSat 24 and 15. Ascending step tests using 1200 cycles at each step. After this number of cycles, the hardening rate is so slow that extended cycling is needed to show that saturation has not occurred. ASat: 20,000 cycles used to prove saturation at each step for low strain amplitudes. 150 cycles are sufficient to cause saturation at high amplitude.

Fig. 2 Cyclic stress-strain curves for larger-grained copper subjected to ascending step tests. MNSat and MLSat refer to results after 1200 and 10,000 cycles at each step, respectively. MHSat results apply to specimens of intermediate grain size after cyclic softening has been produced by extended cycling.

Fig. 3 Predictions based on the planar double slip model of: (a) h/σ versus band angle for various values of the hardening parameter $p=h_{22}/h_{11}$ and (b) the $(h/\sigma)_{cr}$ versus p , where the critical value corresponds to the maximum of the curve in (a).

Case 3i - single slip

Fig. 4 Based on the full three-dimensional geometry for FCC copper in single slip orientations, predictions of shear band initiation (bifurcation point) which corresponds to the terminus of the τ - ϵ curves and an example of the variation in the instantaneous hardening modulus on each active slip system, where B4 is the primary slip system.

Case 2

Fig. 5 Based on the full three-dimensional geometry for FCC copper in a double slip orientation, predictions of shear band initiation (bifurcation point) which corresponds to the terminus of the τ - ϵ curves and an example of the variation in the instantaneous hardening modulus on each active slip system, where B4 and C1 are the primary and conjugate slip system.

UNIVERSITY OF PENNSYLVANIA
PHILADELPHIA, PA 19104-6272

RESEARCH PROPOSAL

Submitted to
UNITED STATES DEPARTMENT OF ENERGY

Title: "The Roles of Slip Geometry and Hardening Behaviour in Intergranular Toughness."

Principal Investigator: Campbell Laird
John Bassani

Position: Professor
Professor

School: School of Engineering & Applied Science

Department: Materials Science and Engineering

Starting Date: January 14, 1992

Duration: 12 months

Funds Requested: First Year: \$138,538
Subsequent Year(s):
TOTAL: \$138,538

Corporate Name: THE TRUSTEES OF THE UNIVERSITY OF PENNSYLVANIA
(A Pennsylvania Non-Profit Organization)

IRS Identification Number: 23-1352685

Congressional District: First Congressional District

Contracting Office: OFFICE OF RESEARCH ADMINISTRATION
Suite 300, 133 South 36th Street
Philadelphia, PA 19104-6205
(215) 898-7293
ATTN: Director of Research Administration

Date: November 6, 1991

By:
Principal Investigator Date

Principal Investigator Date

Approved:
Charles J. McMahon, Jr. Date
Department Chairman MSE

David Pope Date
Department Chairman MEAM

Approved:
Dean Gregory C. Farrington Date

Berenice N. Saylor
Asst. Dir. / PA / Admin

PROPOSAL:

"The Roles of Slip Geometry and Hardening Behaviour in Intergranular Toughness"
January 1992 through January 1993

The goal of the research is to understand the micromechanics of deformation and fracture at grain boundaries, building on the developments of bicrystal experimentalists. The bicrystal approach has proven so useful in earlier work that we propose to continue using it here, initially for monotonic loading and subsequently for cyclic loading.

During the present year, we have developed methods of processing our bicrystals and selecting specific bicrystal misorientations, in line with our initiative proposal. We now propose to go ahead with the experiments, focusing on deformation techniques, employing the "sharp corner" technique for relating deformation adjacent to the boundary to the fracture that is occurring in the boundary, and comparing the behaviour of copper with that of Cu-Al multicrystals, having a planar slip character. Studies of dislocation structures by TEM will be used to guide the continuum mechanical calculations, proposed to be done in conjunction with the experiments. Developments in this area have been very encouraging in the last year.

END

**DATE
FILMED**

01109192