DO

DOE/PC/88818--11

DE92 008702

**TWO-STAGE, CLOSE COUPLED
CATALYTIC LIQUEFACTION OF COAL
ELEVENTH QUARTERLY REPORT FOR THE PERIOD
1 APRIL 1991 - 30 JUNE 1991**

A.G. COMOLLI
E.S. JOHANSON
S.V. PANVELKER
G.A. POPPER
R.H. STALZER

**WORK PERFORMED UNDER CONTRACT
DE-AC22-88PC88818**

HYDROCARBON RESEARCH, INC.

100 OVERLOOK CENTER, SUITE 400
PRINCETON, NEW JERSEY 08540

OCTOBER 1991

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

**TWO-STAGE, CLOSE COUPLED
CATALYTIC LIQUEFACTION OF COAL
ELEVENTH QUARTERLY REPORT FOR THE PERIOD
1 APRIL 1991 - 30 JUNE 1991**

A.G. COMOLLI

E.S. JOHANSON

S.V. PANVELKER

G.A. POPPER

R.H. STALZER

WORK PERFORMED UNDER CONTRACT
DE-AC22-88PC88818

HYDROCARBON RESEARCH, INC.
100 OVERLOOK CENTER, SUITE 400
PRINCETON, NEW JERSEY 08540

OCTOBER 1991

PRINTED IN THE UNITED STATES OF AMERICA

AVAILABLE FROM:

**National Technical Information Center
U. S. Department of Energy
5285 Port Royal Road
Springfield, Virginia 22161**

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Department of Energy, nor any of their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, mark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendations, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

	<u>PAGE</u>
ABSTRACT	1
SUMMARY	2
INTRODUCTION	3
TASK 2 -LABORATORY SCALE STUDIES	4
Evaluation of Rejuvenated/Regenerated Catalysts	4
Evaluation of Recovered Catalysts	8
TASK 3 -BENCH-SCALE STUDIES	10
Run CC-13 - CO ₂ Coal Studies	10
Run CC-14 - Evaluation of a Pre-Dispersed Iron Oxide Hydroxide Catalyst	12
TASK 4 -MINI PDU	27
TASK 5 -TECHNOLOGY ASSESSMENT	27
TASK 6 -ADMINISTRATION	28

ABSTRACT

This quarterly report covers activities of the Two-Stage, Close-Coupled Catalytic Liquefaction of Coal program during the period April 1, - June 30, 1991, at Hydrocarbon Research, Inc., in Lawrenceville and Princeton, New Jersey. This DOE contract period is from October 1, 1988 to December 31, 1991.

The overall purpose of the program is to achieve higher yields of better quality transportation and turbine fuels and to lower the capital and production costs in order to make the products from direct coal liquefaction competitive with other fossil fuel products.

The quarterly report covers work on Microautoclave Testing, Bench-Scale experimentation, Technology Assessment, Modelling and scheduling.

SUMMARY

The second calendar quarter of 1991 concluded a series of bench-scale studies prior to a PDU run on Wyoming Black Thunder coal.

In Laboratory Scale Studies, rejuvenated and regenerated catalysts were evaluated and compared at various stages of preparation. The rejuvenated catalyst compared favorably with fresh catalyst. Spent catalysts from the Bench-Scale evaluation of rejuvenated catalyst were also examined on a micro-autoclave scale along with catalysts from previous bench studies.

A 20 1/3 day run was completed evaluating a PETC catalyzed coal using a pre-dispersion technique to precipitate iron catalyst on the coal and comparing its performance with molybdenum catalyzed and thermal operation.

Performance of the iron oxide hydroxide catalyst was very good at mild conditions, comparing favorably with molybdenum and supported catalyst.

The mini PDU run is scheduled to occur in the October-November time frame.

INTRODUCTION

The studies conducted in this, the eleventh quarterly report of Contract No. DE-AC22-88PC88818, are reported by task and in sequence.

Task 1 is the Management Plan and is complete. Task 2 is for Laboratory Studies and includes microautoclave and microreactor work. Task 3 is for Bench-Scale studies and in this report covers results of Runs CC-12, and 13. Task 4 is for Mini PDU Scale-up. Task 5 is the Technical Assessment, including Modelling, Design and Economics. Task 6 is Administration.

The contract period was from October 1, 1988, to September 30, 1991, and has been extended to December 31, 1991.

TASK 2 - LABORATORY STUDIES

EVALUATION REJUVENATED/REGENERATED CATALYSTS

The rejuvenated CTSL catalyst charged to bench unit Run CC-12 has been evaluated in the microautoclave for residual oil conversion activity, hydrogen addition, and denitrogenation performance. The test program included comparison with the performances of fresh S-317 catalyst, the recovered CTSL catalyst used to prepare the rejuvenated catalyst, the acid-washed catalyst produced in the course of preparing the rejuvenated catalyst, regenerated catalyst (without acid washing), acid washed catalyst regenerated to three different carbon contents, and recovered first and second stage catalysts from Run CC-12.

Table 1 summarizes the results of these microautoclave tests.

The program showed that the rejuvenated catalyst had catalytic performance very nearly that of fresh S-317 catalyst, acid washing alone had only a partial restoration of catalytic activity while regeneration (without acid washing) was very nearly as effective as the rejuvenation procedure, optimal regeneration might be at a lower severity than used in preparing the rejuvenated catalyst. The recovered second stage catalyst from Run CC-12 was considerably more deactivated than the recovered first stage catalyst.

- 1) The recovered CTSL catalyst used in preparing the Rejuvenated used in Run CC-12 was less active than fresh (presulfided) Catalyst (compare Runs CE32 and CE36):
 - A) Nominally 56% as active for residual oil conversion (relative first order rate constant - $\ln(C_{\text{feed}}/C_{\text{prod}})$);
 - B) The hydrogen content increased by only 0.26 W% compared to 0.57 W%;
 - C) The nitrogen content was lowered by only 0.20 W% compared to 0.37 W%;
- 2) The activity of the rejuvenated catalyst charged to run CC-12 approached that of fresh catalyst (compare Runs CE33 and CE36):
 - A) The nominal residual conversion activity was 93% that of fresh catalyst;
 - B) Hydrogen content was increased by 0.46 W% (vs 0.57W%);
 - C) Nitrogen content was lowered by 0.39 W/% (more than by fresh catalyst, 0.37 W%);
- 3) Acid Washing alone gave a relatively small improvement in catalyst performance (Run CE37):
 - A) The nominal residual oil conversion activity increased to 69% of fresh catalyst (from 56%);

- B) The hydrogen content increase was 0.32 W% (up from 0.26 W%);
 - C) The nitrogen content was lowered by 0.23 W% (compared to 0.20 W%);
- 4) Regeneration alone (without acid washing) resulted in catalyst performance very comparable to that of the rejuvenated catalyst (Run CE41):
- A) The nominal residual oil conversion activity, at 97% of that of fresh catalyst, was slightly higher than that of the rejuvenated catalyst, 93%;
 - B) The increase of hydrogen content, 0.42 W%, was slightly less than that with rejuvenated catalyst, 0.46 W%;
 - C) The decrease in nitrogen content, 0.31 W%, was appreciably less than that with rejuvenated catalyst, 0.39 W%;
- 5) A series of tests with acid washed catalyst regenerated to various carbon contents indicated the following (Runs CE38, CE39, and CE40). These samples were from the various batches of regenerated material combined as the L-759 composite:
- A) Lowering the carbon content to 9.0 W%, from 18.7 W%, resulted in only partial recovery of catalytic activity, to 82% of fresh catalyst residual oil conversion activity, and comparable performance with regard to hydrogen uptake and nitrogen removal;
 - B) The regenerated sample with 4.0 W% carbon gave the highest residual oil conversion activity, almost exactly equal to that of the fresh catalyst. However, hydrogen addition and denitrogenation were slightly below that of the fresh catalyst or of the rejuvenated composite, which contained 0.73 W% carbon.
 - C) The regenerated sample containing 1.55 W% carbon had values of the three performance parameters very close to those with the composited L-759 rejuvenated catalyst. This degree of agreement might be regarded as the reproducibility of the test procedure.
- 6) The first and second stage catalysts recovered after CTSL Run CC-12 were also evaluated in the microautoclave with the following results (Runs CE34 and CE35):
- A) The second stage catalyst had been appreciably more deactivated than the first stage catalyst to 45% of fresh catalyst residual oil conversion activity compared to 70% for the first stage catalyst, and only 0.19 W% hydrogen addition compared to 0.38% for the first stage catalyst. The product nitrogen contents were the same for these two tests, but very small effects would be expected after considering the results of the other microautoclave tests;

- B) The averages of the three performance parameters for first and second stage catalysts from Run CC-12 were very close to the performance parameters for the original L-758 recovered catalyst (which was a composite of first and second stage catalysts) used in preparing the rejuvenated catalyst. This result indicates no extraordinarily great rate of deactivation for the rejuvenated catalyst, although the Run CC-12 operation processed 325 lbs coal/lb catalyst/stage, while the operations of the CTSI recovered catalyst used in preparing the rejuvenated catalyst charge to Run CC-12 had processed about 1121 pounds coal per pound of catalyst in a sequence of runs.

TABLE 1

MICROAUTOCLAVE TESTING OF REGENERATED AND REJUVENATED CTSL CATALYST

Microautoclave Product, W%									
MA Run	Catalyst Carbon ³	Residium	Hydrogen	Nitrogen ⁴	Sulfur	Relative Resid Rate Constant	Hydrogen Change	Nitrogen Change	
Feed to Microautoclave Tests									
Catalyst									
Fresh S-317 ¹	0.00	29.34	8.53	0.57	0.04	1.00	0.57	-0.37	
L-758 Recovered Catalyst to Rejuvenation	17.26	14.08	9.10	0.20	0.14	0.56	0.26	-0.20	
L-759 Rejuvenated Catalyst to Run CC-12 ¹	0.73	19.46	8.79	0.37	0.14	0.93	0.46	-0.39	
Acid Washed L-758 ¹ Regenerated L-758 (Not Acid Washed) ^{1,2}	18.71 1.38	14.78	8.99	0.18	0.16	0.69 0.97	0.32 0.42	-0.23 -0.31	
Acid Washed L-758 Regenerated to 9.0% Carbon ¹	9.00	17.63	8.85	0.34	0.18	0.82	0.36	-0.29	
Regenerated to 4.0% Carbon ¹	4.08	14.42	8.77	0.22	0.20	1.00	0.44	-0.35	
Regenerated to 1.55% Carbon ¹	1.55	15.05	8.99	0.20	0.27	0.91	0.46	-0.37	
Recovered Catalyst From Run									
CC-12									
First Stage	11.14	17.59	8.91	0.32	0.04	0.70	0.38	-0.25	
Second Stage	15.44	21.08	8.72	0.31	0.15	0.45	0.19	-0.26	
Average		19.34	8.81	0.32	0.14	0.57	0.28	-0.25	

¹ Catalyst Presulfided in Microautoclave: 2 hours, 550°F, 1,500 psig (H₂) with 38% TNPS in Tetralin, 4/1 Solvent/Catalyst
² Regenerated in Laboratory, 850°F, 2% Oxygen
³ Carbon on Catalyst to Presulfiding or to Microautoclave Test.

Microautoclave Tests:
825°F, 30 minutes, 2,000 psig (H₂)
1 gram CTSL PFL/Gram estimated contaminant-free catalyst

EVALUATION OF RECOVERED CTSL CATALYSTS

In addition to the evaluation of the first and second stage catalysts from CTSL Run CC-12, which was discussed in the section above, first and second stage catalysts from Runs CC-8, and CC-11 were similarly evaluated in the microautoclave. *Table 2* summarizes the results of these microautoclave tests.

CTSL Bench Unit Run CC-8 processed Illinois No. 6 Coal that had been cleaned by the Otisca Process to reduce the ash content to 3.5 W%. CTSL Bench Unit Run CC-11 processed Black Thunder Mine (Wyoming) coal. The catalyst for both runs was Shell S-317 catalyst, which was presulfided, using TNPS doped gas-oil at temperatures of 450-650°F, as part of the start-up operations of the run. During Run CC-11 H₂S was added, corresponding to 2 W% of the coal, so as to maintain the sulfided level of the catalyst. No H₂S was added during Run CC-8 since with the higher sulfur content Illinois Coal the H₂S formation was equivalent to this proportion.

The current microautoclave tests included a contemporary series of tests using Shell S-317 catalyst, HRI 5394P, which had been pre-sulfided somewhat similarly to the CTSL Bench Unit procedure, although in a small fixed bed. This series of tests was intended to supply a reference data base for "fresh" catalyst to use in comparison with the results for the recovered CTSL catalysts.

Referring to *Table 2*, all four of the recovered catalysts showed appreciable activity in converting the residual component in a recycle solvent obtained during CTSL Bench Unit operations with Black Thunder Mine coal in Run CC-1. The residual oil conversion levels with the recovered catalysts were higher than obtained with half as much "fresh" catalyst, but lower, in three cases, than obtained with about the same amount of "fresh" catalyst. The first and second stage catalysts from Run CC-8 had about the same catalyst effectiveness, 77-83% of that of "fresh" catalyst as these microautoclave tests have been correlated. In contrast, the first stage catalyst from Run CC-11 was considerably more effective than the second stage catalyst from that run. Actually, this first stage catalyst demonstrated an activity even higher than that of the "fresh" catalyst, while the second stage catalyst was only 71% as effective as the "fresh" catalyst.

The relative effectiveness of the four recovered catalyst that were tested corresponded to their carbon contents (noted in *Table 2*), with the least effective catalyst containing 18.8% carbon, and the most effective 10.0% carbon, and the catalysts of intermediate effectiveness having intermediate carbon contents.

There were a pair of replicate tests with the "fresh" catalyst, Runs CM103 and CM105, which indicates the sensitivity of the microautoclave tests to the analytical results, where a difference of less than 1 W% in analyzed residual oil content corresponds to a difference of over 20% in indicated catalyst effectiveness. This is because the conversion pattern with increasing catalyst/oil ratio does not follow simple first-order kinetics so that deeper residual conversions require disproportionate increases in catalyst effectiveness. The correlating equations indicated in *Table 2* correspond to system with two residual oil components of differing reactivity, both following first-order kinetics.

TABLE 2

MICROAUTOCLAVE TESTS WITH RECOVERED CATALYSTS FROM CTSL OPERATIONS

825°F, 2,000 psig H₂, 30 Minutes with CTSL Recycle Solvent (PFL)

CTSL Run	CC-8	CC-8	CC-11	CC-11	--- Presulfided Shell S-317 Catalyst ---		
Stage	First	Second	First	Second			
Coal Feed	Illinois No. 6				Black Thunder		
Cat. Age, Lb Coal/Lb	560	560	748	748			
Catalyst Analysis							
Carbon, W%	12.56	13.61	10.34	18.82	----- 5.81 -----		
Sulfur, W%	6.32	6.02	6.34	5.48	5.24		
Metal Contam., W%	0.97	1.12	2.35	2.45	-----		
Molybdenum, W%	7.46	7.39	8.25	7.78	9.49		
Microautoclave Run	CM99	CM100	CM101	CM102	CM103	CM105	CM104
							CM106
Catalyst/Oil As Charged Equivalent	1.00 0.79	1.00 0.78	1.00 0.87	1.00 0.82	1.00 1.00	1.00 1.00	0.50 0.50
							0.25 0.25
Product Residuum, W%''	20.73	20.68	18.39	20.94	18.61	19.58	21.39
							24.64
Relative Catalyst Activity	0.81	0.83	1.39	0.74	1.14	0.86	(1.00)
Activity	0.77	0.79	1.21	0.71	1.00	0.79	(1.00)

Relative contaminant-free catalyst, based on molybdenum content relative to that of presulfided catalyst.

TGA analysis, CTSL feed to tests contained 29.87 W% residue (Run CC-1, Period 23 PFL).

Presulfided Catalyst correlated as $C = Co * (0.70 * Exp(-0.1165 * (Cat/Oil)) + 0.30 * Exp(-2.996 * Cat/Oil))$

Presulfided Catalyst correlated as $C = Co * (0.70 * Exp(-0.1462 * (Cat/Oil)) + 0.30 * Exp(-2.813 * Cat/Oil))$

TASK 3 - BENCH SCALE STUDIES

RUN CC-13 (227-71) CO₂ AND LIGHT DISTILLATE SLURRYING

The principal results of Run CC-13, which evaluated CO₂ or a vaporizable distillate as feed slurring agents for Black Thunder Mine coal in the CTSL process, were summarized in the previous Quarterly Report. The analyses of the first and second stage catalysts recovered after the operations of that run have become available, and are summarized in *Table 3*.

The catalysts from both stages recovered after Run CC-13 were highly contaminated, with carbon contents higher than contained on the corresponding catalysts recovered after previous CTSL runs with Black Thunder Mine coal. The first stage catalyst contained 17.6 W% carbon, which compares to values of 15.6%, 11.4%, 8.9%, 13.6%, 10.0%, and 11.4% for recovered first stage catalysts after the earlier runs with Black Thunder Mine coal. The second stage catalyst after Run CC-13 contained 31.4 W% carbon, which is exceptionally high compared to values of 18.9%, 13.1%, 18.2%, 18.8%, and 15.4% for second stage catalysts after those earlier runs. It does not appear that these Run CC-13 carbon accumulations were associated with loss of ebullation during the run since the unit was operating in good order with a slightly elevated pressure drop during the final coal operations and the subsequent shut-down operations. The catalysts were in the normal settled positions in the reactor and recovered from the reactors as loose extrudates, although there was a thin plug about half way up in the settled bed in the second stage reactor and a small amount of catalyst in the screen at the top of the that reactor. The elevation in pressure drop from a normal level of about 3 psi to about 20 psi across the second stage reactor first appeared during the twelfth day of the run during the attempted operations using a light distillate (480°F average boiling point) for slurring the coal in place of recycled filtered liquid. This elevated pressure drop persisted with the returned to normal slurring practice in the thirteenth day to the end of run after 19 days.

There was a considerable loss in pore volume and surface area associated with the very high carbon accumulation on the recovered second stage catalyst, with a pore volume about one-third, and surface area one-tenth, of that of fresh catalyst.

TABLE 3
RECOVERED CATALYST ANALYSIS
RUN 227-71 (CC-13)

STAGE	First	Second
Catalyst Age, Lb Coal/Lb	541	537
<u>Catalyst Recovery</u>		
Volume (compacted), cc	775	680
Weight, grams	637	760
Bulk Density, Gm/cc	0.821	1.118
<u>Analyses of Oil-Free +20 Mesh Catalyst, W%</u>		
Carbon	17.60	31.44
Hydrogen	1.12	0.97
H/C Ratio	0.76	0.37
Nitrogen	0.30	0.23
Sulfur	5.43	5.26
Molybdenum	7.52	5.95
Nickel	1.63	1.28
Titanium	0.03	0.02
Iron	0.45	0.10
Calcium	0.59	0.29
Sodium	0.82	0.85
Total Metal Contaminants	1.89	1.24
Loss on Ignition, W%	20.44	40.98
Particle Density, Gm/cc particle	1.329	1.655
Pore Volume (D>30°A), cc/gm	0.296	0.124
cc/cc particle	0.393	0.205
Surface Area (calc.), M ² /gm	141	15
M ² /cc particle	187	25
<u>Modal Pore Diameter, Angstrom</u>		
Macro-pores		1,930
Mini-pores	61	
<u>Analysis of Ignited Catalyst</u>		
Particle Density, Gm/cc particle	1.069	1.080
Pore Volume (D>30°A), cc/gm	0.557	0.563
cc/cc particle	0.595	0.608
Surface Area (calc.), M ² /gm	204	190
M ² /cc particle	218	205
<u>Modal Pore Diameter, Angstrom</u>		
Macro-pores		2,190
Mini-pores	91	96
<u>Analysis of -100 Mesh Oil-Free Solids</u>		
Weight, Grams	64	92
Molybdenum, W%	1.53	3.52
<u>Analysis of -100 Mesh Oil-Free Solids</u>		
Weight, Grams	53	50
Molybdenum, W%	0.31	1.41

* In mercury at 10 psia

RUN CC-14 - EVALUATION OF A PRE-DISPERSED IRON OXIDE HYDROXIDE CATALYST

A 20 1/3 day study was conducted with a pre-dispersed iron-oxide hydroxide catalyst that included a comparison with molybdenum and a non-catalytic operation.

EXPERIMENTAL PLAN

The original plan specified an 18 day operation, however due to a mid-run flow interruption, the operation was extended to 20 1/3 days at five conditions, three with FeOOH, one with no additive and one with Ammonium Tetrathio-Molybdate added to the slurry. The space velocity, backpressure, H₂S addition rate, second stage temperature and oil/coal ratio were held constant throughout the run after initial adjustment early in condition 1 of the feed slurry concentration. A preheater temperature of 527°F (275°C) was used. The original plan called for lowering the pretreater reactor temperature to less than 400°F during the condition with molybdenum based catalyst as the work at PETC indicated that the pretreatment was not required to activate the catalyst; however, it was necessary to operate at 527°F as a result of line plugging problems.

TABLE 4

EXPERIMENTAL PLAN, CC-14
EVALUATION OF DISPERSED CATALYST

Condition	1	2	3	4	5
Periods	1-5	6-10A	11A-15A	15B-18A	18B-21A
Dispersed Catalyst	FeOOH	FeOOH	ATTM	None	FeOOH

Temperatures, °F

Pretreatment	527	527	450-525	527	527
Second Stage	800	825	825	825	825
Third Stage	775	775	775	775	775

Other

Pressure, Psig - 2,500

H₂S, W% Coal - 3%

Oil/Coal Ratio - 1.6

COAL

The feed was an Illinois #6, Burning Star Mine coal pulverized to -200 mesh (See Table 5). The catalyzed coal was prepared by DOE-PETC using an incipient wetness impregnation/precipitation method. A solution of one part ferric nitrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$) dissolved in 40 parts distilled water was used to wet 50 parts of -200 mesh coal to incipient wetness (paste). The wet coal paste was then added into a solution containing 20 parts ammonium hydroxide (29% NH_3) and 200 parts distilled water. This mixture was then pressure-filtered through 0.45 micron media to obtain a clear filtrate. The iron catalyzed coal was then vacuum dried at 104°F.

Pulverized untreated Illinois coal was used for the baseline and for the molybdenum catalyzed bench unit conditions.

CATALYSTS

The supported catalyst in the second stage reactor was Shell 317, a commercial NiMo 1/32" diameter extrudate with a bi-modal pore distribution. Dispersed catalysts were the precipitated FeOOH at 2,800 ppm Fe on a coal basis and molybdenum sulfide added at 10% solution in water as ammonium tetrathiomolybdate. This was mixed into the coal feed slurry to obtain a moly concentration of 1,500 ppm on a coal basis.

TABLE 5

ILLINOIS #6 COAL ANALYSIS

	<u>Treated</u>	<u>Untreated</u>
<u>Ultimate, W% Dry</u>		
Carbon	68.78	68.6
Hydrogen	4.32	4.29
Sulfur	3.19	3.39
Nitrogen	1.58	1.26
Ash	11.00	10.83
Oxygen (by difference)	11.13	11.63
 <u>Ash Analysis, W% Ignited</u>		
Silicon Dioxide	46.3	47.1
Aluminum Oxide	18.1	17.9
Potassium Oxide	1.7	1.8
Iron Oxide	20.6	17.2
Sulfur Trioxide	5.4	7.3

All others less than 1%

OPERATIONS

Following presulfiding of the sulfided NiMo catalyst with injected H_2S and an Illinois coal derived heavy distillate, catalyzed coal was introduced and operations proceeded smoothly until an interruption of flow occurred during a planned transition to a lower temperature prior to condition 3. A line plug was removed and the unit restarted in one day, operations then were steady with the exception of some foaming from moist coal in condition 5.

PRODUCT YIELDS

Coal conversion ranged from 94 to 95 W% (MAF) as shown in *Table 6*. Dispersed catalyst had an insignificant effect on coal conversion. Interstage samples obtained after condition 2 through 5 indicated that all the coal conversion (94+%) occurred in the second stage with the third stage performing residuum conversion and product upgrading.

The highest distillate yields (74.5%) in the study were obtained in condition 1 with FeOOH dispersed coal at the least severe first stage (800°F) temperature and the next highest in conditions 3 with the added molybdenum catalyst. *Table 6* and Figure 1 and 2 attached show the performance at each operating condition. The unanticipated poorer performance in condition 5 may have been the result of several factors; among these are: (1) the intermittent addition of moist coal impacting hydrogen partial pressure and (2) not achieving equilibrium following the uncatalyzed coal operation in condition 4. An indication of the latter is supported by the interstage samples taken at the end of each condition; these results are shown in Figure 3. Note that the H/C ratio of the mid-distillate cuts is continuing to increase after condition 5 while the H/C ratio of the recycle PFL (pressure filter liquid) existing in the second stage is continuing to decrease, Figure 4. Further evidence of non-equilibrium operation is shown in a plot of PFL sulfur content in Figure 5. The sulfur content of the distillate continues increasing in the thermal condition 4 through repeat FeOOH condition 5.

The yields in conditions 1 and 2, as shown in Figure 6, illustrate the selectivity of FeOOH catalyst at two thermal severities. Light gas (C_1-C_3) yield increases by nearly 4% and naphtha by nearly 6% resulting in increased hydrogen consumption, 8.2 vs 7.5% and lower total distillate production. The distillate yield increased by more than 2% when the catalyst was changed from Fe to Mo and decreased by more than 4% in the transition to no added dispersed catalyst in condition 4.

The quality of the liquid products from the run are exemplified by the atmospheric still overhead products (250-650°F) as shown in *Table 7*. In terms of hydrogen content and heteroatom content, the best quality is found at conditions 1 and 3 with the FeOOH catalyst at mild conditions and with the molybdenum catalyst.

TABLE 6

**CONTINUOUS BENCH-SCALE
EVALUATION OF DISPERSED FeOOH AND
AMMONIUM TETRATHIO-MOLYBDATE**

Condition Additive Amount	1 FeOOH 2,800 ppm	2 FeOOH 2,800 ppm	3 ATTM 1,500 ppm	4 None --	5 FeOOH 2,800 ppm
<u>Reaction Temp., °F</u>					
Pretreater	525	527	523	528	527
First Stage	799	825	822	822	825
Second Stage	775	775	775	774	774
<u>Yields, W% MAF Coal</u>					
C ₁ -C ₃	8.6	12.3	11.5	12.0	12.5
C ₄ -390°F	20.7	26.5	24.0	21.7	23.3
390-650°F	34.9	32.3	33.1	31.9	30.6
650-975°F	19.5	10.2	14.7	13.6	11.8
975°F ⁺	5.7	3.6	4.6	7.3	7.4
<u>Performance, W% MAF Coal</u>					
C ₄ -975°F	75.1	69.0	71.8	67.2	65.7
975°F ⁺ Conversion	88.0	90.4	89.5	86.4	87.5
Hydrogen Consump. W%	7.5	8.2	8.1	7.4	7.8
Coal Conversion	94.0	94.6	94.5	94.2	95.0

DISPERSED CATALYST RUN (CC-14) DISTILLATE YIELD

FIGURE 1

DISPERSED CATALYST RUN (CC-14) HYDROGEN CONSUMPTION

FIGURE 2

DISPERSED CATALYST RUN (CC-14) H/C RATIO OF 1ST STAGE SAMPLE CUTS

FIGURE 3

DISPERSED CATALYST RUN (CC-14) H/C RATIO OF PFL CUTS

FIGURE 4

DISPERSED CATALYST RUN (CC-14) SULFUR CONTENT OF PFL CUTS

FIGURE 5

DISPERSED CATALYST RUN (CC-14) PRODUCTS YIELD WITH FE CATALYST

FIGURE 6

TABLE 7

ANALYSIS OF ATMOSPHERIC OVERHEADS

Condition	1	2	3	4	5
API Gravity	23.9	25.0	25.8	23.0	22.9
Carbon, W%	87.4	87.2	87.0	87.0	86.9
Hydrogen, W%	11.6	11.4	11.7	11.2	11.1
Nitrogen, W%	0.14	0.19	0.15	0.2	0.25
Sulfur, W%	<0.01	0.02	0.04	0.11	0.13
H/C Ratio	1.60	1.57	1.61	1.55	1.53
Watson Factor	10.8	10.8	10.8	10.7	10.7

SUMMARY AND CONCLUSIONS

The iron-based chemically dispersed catalyst performed very well with distillate yields C_4 -975°F of over 75 W% of MAF coal with the first stage at 800°F and the second ebullated-bed stage at 775°F. Increasing the thermal severity to 825°F lowered the distillate yield and increased hydrogen consumption by producing more C_1 - C_3 gases. Molybdenum based dispersed catalyst appears to yield better or equivalent performance with respect to residuum conversion and product quality; however, the relative performance may be over shadowed by deactivation of the supported catalyst in the ebullated-bed reactor.

Further optimization of the FeOOH catalyst formulation and operating conditions are warranted based on the results of this study. The yields in condition 1 approach the maximum obtained at HRI with two ebullated-bed reactor stages. See *Table 8* for a comparison, although the coal shipments, time periods and cleaning techniques differ, the overall performance is similar.

RECOMMENDATIONS

Following the complete analysis of the spent ebullated-bed catalyst from this study and a complete metals balance, further studies to optimize operating conditions with Illinois coal are recommended. In addition the activity of this chemically dispersed iron catalyst should be investigated with sub-bituminous coal, a coal more difficult to convert but one that produces a more easily convertible residuum.

TABLE 8

**A COMPARISON ILLINOIS #6 COAL PROCESSING WITH FeOOH
CATALYST AND SUPPORTED CATALYSTS¹**

Catalyst	FeOOH	NiMo
Process	Pretreat Stage First Stage Back- Mixed Second Stage- Ebullated	Ebullated-Bed Two Stages
Catalyst Age, lbs coal/lb cat. Stage 2	145	233
<u>Reaction Temperature, °F</u>		
Pretreater (First Stage)	525	--
Second Stage	800	750
Third Stage	775	800
<u>Performance, W% MAF Coal</u>		
C ₄ -975°F	75.1	76.2
975°F+ Conversion	88.0	90.2
Hydrogen Consumption, W%	7.5	7.4
Coal Conversion	94.0	95.4

¹Different Shipments of Illinois #6 Coal.

TASK 4 - MINI-PDU SCALE-UP

Preparations

Work commenced on the design and purchase of components of the U.S. Filter Installation, Slurry Mix Tank Ventilation System, Gas and Oil Purge System Improvements, DMDS Feed Station and new reactor configuration.

TASK 5 - TECHNICAL ASSESSMENT

Process Modelling

A PDU Run Plan for the Extinction Recycle of Black Thunder Coal is being prepared using the latest process models derived from Bench-Scale and Micro-Scale Studies.

TASK 6 - ADMINISTRATION

In the balance of the current contract the PDU scale-up demonstration run remains. Topical reports for the Bench-Scale and Laboratory-Scale Studies are being prepared.

A paper entitled "CTSL™ Catalytic Two-Stage Liquefaction Coupled with Coal Cleaning" was presented at the 201st National ACS Meeting in Atlanta Georgia on April 14-19, 1991. A paper entitled "Recent Advances in Direct Coal Liquefaction" was presented at the 16th International Conference on Coal & Slurry Technologies on April 22-25, 1991,

The attached schedule shows the run activities for the remainder of the contract.

END

DATE
FILMED

4/7/92