TECHNICAL DIVISION
SAVANNAH RIVER LABORATORY

Key Words: In-situ tests, waste glass, Ballidon, UK, HLW, limestone

Authorized Derivative Classifier:

Retention Time: December 1999

Received by OSTI
MAR 19 1992

February 26, 1991

TO: D.L. McIntosh, 773A
J.L. Steele, 773A
E.W. Holtzscheiter, 773A
M.J. Plodinec, 773A

N.E. Bibler, 773A
C.M. Jantzen, 773A
B.G. Kitchen, 773-41A
SRL File (4), 773A

FROM: C. G. Namboodri Jr.*, 773-A
G. G. Wicks, 773-A *gw*

SRL In-Situ Tests in the United Kingdom:
Part II: Surface Analyses of SRS Waste Glass Buried for
One and Two Years in Limestone at Ballidon, UK (U)

INTRODUCTION

A primary objective of high level waste management activities at the Savannah River Site (SRS) is to safely and effectively immobilize 34 million gallons of high level radioactive waste (HLW) currently being stored on-site. This will be achieved by first separating, and then concentrating, the highly radioactive portion of the waste. The waste will be processed, conditioned and radionuclides within immobilized into borosilicate glass. This will be accomplished mainly in the Defense Waste Processing Facility (DWPF), which has recently been constructed at SRS. The solid waste products produced will be placed in temporary storage in an adjacent interim storage building, but ultimately, all waste glass forms produced at SRS, will be shipped away from the site to carefully selected federal, geologic repositories [1,2]. Here they

* COOP student from Clemson University

will be permanently disposed in deep burial as part of a multibarrier isolation system. Therefore, it is important to demonstrate that high integrity waste glass products will be produced at SRS and will ultimately perform well in a geologic environment.

A multiphase experimental program to assess and understand waste glass behavior under a wide range of conditions has been in progress at the Savannah River Laboratory (SRL) for over a decade [3, 4]. An important part of this experimental effort is to assess the effects of repository-relevant conditions on performance of SRS waste glass, in both controlled laboratory tests, as well as in actual field experiments [5-7]. In laboratory tests, SRS waste glass, simulated and in many cases also fully radioactive, has been tested in environments of salt, basalt, shale, granite, clay and tuff. In field experiments, there are four joint international programs being conducted in four different countries, involving burial of SRS simulated waste glass in granite, limestone, clay and salt geologies. These field tests are summarized below:

- (1) SWEDEN- granite; a joint program between the Swedish Nuclear Fuel Safety Division of the Nuclear Fuel Supply Co. (SKBF/KBS), the University of Florida (UF), and SRL was begun in 1982 and involves the burial of more than 100 SRS waste glass samples buried in the Stripa mine in Sweden. [8-13],
- (2) BELGIUM- clay; a joint program between the Studiecentrum Voor Kernenergie/Centre D'Etude de L'Energie Nucleaire (SCK/CEN) and SRL was begun in 1986 and involves the burial of simulated SRS waste glass samples in the Belgium underground research laboratory in boom clay, located in Mol, Belgium. [3, 5],
- (3) UNITED KINGDOM- limestone; a joint program between the University of Sheffield and SRL was begun in 1986 and involves the burial of simulated SRS waste glass compositions as well as natural glass analogs in the limestone formation at Ballidon, U.K. [18-20],
- (4) USA- salt; the largest cooperative field testing venture in the international waste management community is the WIPP/SRL program called the Materials Interface Interactions Tests (MIIT). This 5-year effort was started in 1986 and involves the testing of almost 2000 simulated waste form and package component samples from seven different countries, in the salt environment of the Waste Isolation Pilot Plant (WIPP) at Carlsbad, New Mexico. This program is being coordinated by SRL and Sandia National Laboratory and involves the active participation of laboratories and universities from France, Germany, Belgium, Japan, Canada, the U.K., the U.S.

and Sweden. These are the first and only field tests involving burial of simulated nuclear waste glass systems to be conducted in the U.S. [3, 14-17].

The United Kingdom/SRL in-situ testing program was described in Part I of an earlier document [20]. The objective of this report, Part II, is to summarize investigations and results obtained thus far, on performance of SRS waste glasses buried for one- and two-years in the limestone formation at Ballidon.

SUMMARY

- SRL waste glasses exhibited excellent chemical durability after being buried in limestone at Ballidon for up to two years. A methodology was defined that will allow the performance of waste glasses in this geology to be compared with other waste glasses studied in other geologic environments.
- Surface analyses of 165/TDS waste glass, 131/35% waste glass, ARM-1 and basalt compositions, buried for one and two years in limestone at Ballidon, defined two distinct reaction regions that formed. This included an outermost precipitated layer several microns thick (α), attributed primarily to the surrounding geology, and underneath, a glass interaction zone less than one micron thick (β), representative of glass reacting with the environment.
- For all samples studied, the glass interaction zone was extremely small even after two years of burial, indicative of samples with good durability and good performance in the limestone formation. SEM/XES analyses semi-quantitatively determined this thickness to be less than one micron for all samples. This finding was consistent with the more quantitative analyses provided by SIMS, which showed that after one year, this zone was 0.06μ for basalt, 0.2μ for 165/TDS, and 0.6μ for both 131/35%TDS and ARM-1.
- SIMS analyses resolved the glass interaction zone (β) into three more detailed regions; β_0 , β_1 and β_2 . This general methodology of the α and β zones for leached SRL waste glasses has now been seen in each of the SRL in-situ testing programs.
- From SIMS data, surfaces of leached SRL waste glasses were seen to be enriched in non-radioactive cesium and strontium, which are 'stand-ins' for Cs-137 and Sr-90, important radionuclides in actual waste. These data suggest that these components may be tied up in the surface layers or phases formed, thus making their release from the glass even more difficult.

- The outermost precipitated layer was a function primarily of the limestone geology. This layer was generally, non-uniformly distributed over the surface of the glass. For one year samples, WAXD studies did not detect any appreciable amounts of crystallinity, although the deposit was noted by XES to be enriched in components found in the geology. For the two year samples, crystalline phases were observed and indexed. Noted were calcium carbonate, magnesium manganese iron silicate hydroxide, silicon oxide, calcium silicate, and magnesium iron oxide.

BACKGROUND ON THE BALLIDON FIELD TESTS

In October of 1970, Walter Fletcher of the British Glass Industry Research Association in Sheffield initiated a group of experiments involving the burial of glasses in the carboniferous limestone at Ballidon in Derbyshire, United Kingdom (UK). In 1978, these tests were taken over and continued by Professor Roy G. Newton of the University of Sheffield [18, 19]. Prior to a scheduled mound opening and glass retrieval, Prof. Newton requested in a December 1985 communication in Glass Technology that any commercial firm or research organization interested in burying glass samples in an alkaline environment contact him [18]. In March 1986, a series of correspondences between SRL and Prof. Newton began and culminated in the fabrication of glass samples at SRL for the Ballidon in-situ experiment in the UK. Representing SRL in this effort were George Wicks, Carol Jantzen and John Plodinec. The Ballidon tests, involving burial of SRL samples, was officially started on July 1, 1986.

SRL SAMPLE MATRIX

The SRL glasses for the Ballidon tests included three configurations, thirteen glass types, and a total of 46 samples, which are summarized in **Table 1** [20]. Included were '*pineapple slices*' of SRL 165/TDS and 131/35%/TDS compositions, both of which are also included in the field tests underway in Sweden, Belgium, and Carlsbad, N.M. Other '*pineapple slice*' compositions included basalt, which is a natural glass analog to waste glass, and ARM-1, which is a Materials Characterization Center (MCC) approved standard [21]. The sample matrix also contained '*cored samples*' of glass produced by prototypical equipment at the TNX semi-works, including TNX precipitate hydrolysis (PHP) glass and TNX 165/TDS melter glass. Finally, in order to relate the performance of complex waste glass compositions to other compositions and those known to be stable for millions of years, '*one-inch cubes*' of natural glass analogs and stable glass systems were also studied [22-26]. Included

were obsidian from Idaho, basalt from Washington, pure silica glass, Pyrex, SRL 165 waste glass, SRL 131 waste glass, and pure Frit 131 [20]. Glass and waste glass compositions used in the in-situ program at Ballidon are summarized in **Table 2** [20].

In **Figure 1**, the three types of specimens and their geometries used in the Ballidon study are shown. These samples were buried under ambient temperature conditions and approximately 43 inches under the surface into the limestone geology. In **Figure 2**, a photograph and schematic representation is given illustrating burial of SRL glasses at the Ballidon site. Burial time periods include 1, 2, 5, and 16 years.

EXPERIMENTAL PROCEDURES

Specimen Analyses Matrix

Of the 46 samples placed into test for 1, 2, 5, and 16 years, the one- and two-year specimens have been removed and analyzed thus far. Among these samples are 'pineapple slices' of SRL 165/TDS, 131/35% TDS, ARM-1, and basalt glasses. These are the samples evaluated in the present study and are the same compositions used in other in-situ testing programs [3-17]. In another study, the performance of these glass and waste glass systems in field tests involving different geologic media will be compared. In **Figure 3**, the sample matrix and analyses performed for this study are summarized.

Surface and Bulk Analyses

In **Figure 3**, both proposed and completed surface analyses used for investigating the Ballidon specimens are shown. This report describes the results of Scanning Electron Microscope/X-ray Energy Spectroscopy (SEM/XES) and Wide Angle X-ray Diffraction (WAXD) for both the one and two year specimens, and of Secondary Ion Mass Spectroscopy (SIMS) for the one-year specimens only. Additional SIMS and future Fourier Transform Infrared Reflectance Spectroscopy (FTIRRS) will be performed later at Chalmers University in Sweden and at the University of Florida, respectively. The combination of all of these analytical tools provides an integrated study of the Ballidon samples. This study will assess the behavior of SRL waste glass in limestone and will be used to compare these interactions with the interactions of the same glasses in other geologies.

- *SEM/XES Analysis:* Surface characteristics were investigated

using SEM/XES. These tools provided morphological and chemical information on precipitated and leached layers of the glasses. Cross-sectional analysis provided details of interaction zones and provided qualitative assessment of elements present at various depths into the glass. SEM/XES analyses of deposited phases provided morphological and chemical information which was used in conjunction with WAXD investigations in indexing phases present.

- *SIMS Analysis:* Results of SIMS profiles of the one-year Ballidon samples were used to help quantify depths of interaction zones. This analytical technique provides relative amounts of elements versus depth into the specimen from the surface.

- *WAXD Analysis:* Crystalline phases deposited from the limestone geology were characterized using structural information provided by WAXD analysis. Knowledge of these deposits can help to better understand the interaction of waste glasses with the geologic environment.

RESULTS AND DISCUSSION

One-Year Samples

SEM/XES surface analyses show scattered deposits on the one-year Ballidon samples. These are shown clearly on the surface of the ARM reference glass depicted in **Figure 4**. XES analyses characterized the deposits as being composed primarily of five elements; calcium, barium, magnesium, iron, and sulfur. The main elements of the deposits result from the surrounding geology.

In **Figures 5-7**, cross-sectional micrographs of reacted glass surfaces (SEM) and corresponding chemical (XES) and structural (WAXD) characterization are given for 165/TDS, 131/35% TDS and ARM-1 systems. These figures show the existence of non-uniform deposits, that vary in thickness to about several microns in extent. WAXD of the surfaces produced an amorphous profile.

Below the deposits is the glass interaction zone. For all the samples studied after one-year of burial at Ballidon, this zone was found to be very thin. From these analyses alone, we can only determine that the thickness of the interaction zone is less than one micron.

A more detailed analyses of the deposited and glass interaction zones was

obtained from the work of Lodding using SIMS. SIMS profiles for 165/TDS, 131/35% TDS, ARM-1 and basalt systems are shown in **Figures 8-11**. For these analyses, a sample preparation technique was used which reduced or eliminated the relatively thick deposits on glass surfaces, in order to quantitatively study the glass interface underneath. This is reflected in the deposited regions denoted as α on the profiles. The most important region to assess glass performance is the interaction zone, which is denoted as β on the profiles. As noted in these profiles, measured interaction zone depths are approximately 0.2, 0.6, 0.6 and 0.06 microns thick. All these depths are less than one micron and are consistent with the SEM/XES analyses described above. Results of the SEM, XES, SIMS and WAXD analyses for these samples are summarized in **Table 3**.

By analyzing the SIMS depth profiles of various elements through the interaction zone, the glass interaction zone could be further resolved into three more detailed regions. The profiles also showed that cesium and strontium, representing short-lived radionuclides found in production waste glass, were enriched on the glass surface of the 165/TDS and 131/35% TDS waste glass compositions. This indicates that these important constituents may even be more difficult to release to solution than suggested by laboratory leaching data.

Two-Year Samples

SEM/XES surface analyses also show deposits on the two-year Ballidon samples. These are shown on the surface of the 165/TDS waste glass specimen depicted in **Figure 12**. XES analyses show that the deposits are characterized primarily by the presence of calcium, barium, iron, and sulfur. As indicated in the micrograph, surface deposits arising from the limestone geology on the two-year samples are more uniform and their morphology much better developed and defined, compared to sample surfaces examined after one-year of burial (**Figure 4**).

In **Figures 13-16**, cross-sectional micrographs of reacted glass surfaces (SEM) and corresponding chemical (XES) and structural (WAXD) characterization are given for the two-year burial samples of 165/TDS, 131/35% TDS, ARM-1, and basalt compositions. These figures also show the existence of deposits, that vary in thickness to about several microns in extent. While deposit thicknesses were roughly equivalent to that observed on one-year samples, WAXD of two-year surfaces now showed the presence of crystalline phases. This is consistent with the

well-defined morphology noted by SEM. Indexing of the WAXD spectra showed the presence of mainly calcium carbonate, along with silicon oxide and an alkaline earth transition metal silicate hydroxide.

The glass interaction zone under the deposits were also examined. Similar to the those produced after one-year, the interaction zones produced after two-years of burial in limestone were also seen to be very thin- less than one micron in thickness. SIMS analyses have not yet been performed on the two-year burial specimens.

Precipitated and Leached Surfaces

In **Figure 17**, a schematic composite representation of precipitated and leached layers found on SRL waste glass samples buried in Ballidon is shown. This is based upon SEM, XES, and WAXD analyses (**Figures 4-7 and Figures 12-16**) and most importantly, SIMS data (**Figures 8-11**). This representation is consistent with the type of interfaces observed on similar SRL systems buried in the salt geology at WIPP [26]. Shown in the representation is a deposited layer denoted as α . This layer can be considered as two sub-layers; α_0 , an outermost layer characterized by the presence of calcium, barium, magnesium, iron, and sulfur, and a precipitated glass layer, α_1 , characterized by enrichments of barium and calcium from the geology and cesium and strontium leached from the waste glass.

The β glass reaction zone is the most important part of the glass surface for assessing glass interactions and leaching. This zone can be resolved into three distinct regions. Closest to the precipitated layers is the depletion zone, β_0 . This is characterized by the depletion of many glass elements and enrichment of other important species such as cesium and strontium. Cesium and strontium are enriched in this zone and at the deposited/ glass reaction zone interface (α/β). This may be important because it indicates these species may be even less mobile than noted from many laboratory leaching tests. A gradient zone, β_1 , is next, which is characterized by relative enrichment of barium and further characterized by decreases of magnesium, hydrogen, cesium, and strontium and increases in other glass components. The final interaction zone is a diffusional region, β_2 , and is characterized by a decrease in barium content and a leveling off of elements approaching the bulk glass composition. The elemental profiles become relatively constant in the

bulk glass.

CONCLUSIONS

For one- and two-year samples buried at ambient temperature in the limestone geology at Ballidon, UK, precipitated layers and interaction zones were observed for SRL waste glasses, an MCC reference glass, and basalt. For each of these samples, the interaction zones were consistently less than 1 μm after one- and two-years of burial. These data indicate that the compositions exhibited excellent chemical durability during the tests. In **Table 3**, all deposited/precipitated layer and glass interaction zone depths are summarized for the study. The basalt waste glass analog showed the best chemical durability, 165/TDS waste glass the next best, and the 131/35%TDS and ARM compositions the third best performance.

REFERENCES

- [1] U. S. Department of Energy, *Nuclear Waste Policy Act of 1982; Proposed General Guidelines for Recommendation of Sites for Nuclear Waste Repositories*, Federal Register, 10CFR Part 960, 48, No. 26 (1983).
- [2] Wicks, G. G., *Nuclear Waste Glasses, Treatise on Materials Science and Technology, Glass IV*, M. Tomozawa and R. H. Doremus eds., Vol. 26, pp. 57-118 (1985).
- [3] Wicks, G. G., *WIPP/SRL In-Situ and Lab Testing Programs - Part I: MIIT Overview, Nonradioactive Waste Glass Studies*, DP-1706, Savannah River Laboratory, Aiken, SC (1985).
- [4] Plodinec, M. J., Wicks, G. G. and Bibler, N. E., *An Assessment of Savannah River Borosilicate Glass in the Repository Environment*, DP-1629, Savannah River Laboratory, Aiken, SC (1982).
- [5] Wicks, G. G., *Nuclear Waste Vitrification - The Geology connection, J. of Non-Crystalline Solids*, 894, pp. 241-250(1986).
- [6] Wicks, G. G., Robnett, B. M. and Rankin, W. D., *Chemical Durability of Glass Containing SRP Waste-Leachability Characteristics, Protective Layer Formation, and Repository Systems Interactions, Scientific Basis for Nuclear Waste Management V*, Materials Research Society, W. Lutze ed., Vol. 11, pp. 15-24 (1982).

- [7] Bibler, N. E. and Jantzen, C. M., *Materials Interactions Relating to Long-Term Geologic Disposal of Nuclear Waste Glass*, Scientific Basis for Nuclear Waste Management X, Materials Research Society, J. K. Bates and W. B. Seefeldt eds., Vol. 84, pp. 47-66 (1987).
- [8] Clark, D. E., Zhu, B. F., Robinson, R. S. and Wicks, G. G., *Preliminary Report on a Glass Burial Experiment in Granite*, Nuclear Waste Management, Advances in Ceramics, G. G. Wicks and W. A. Ross eds., Vol. 8, pp. 324-336 (1984).
- [9] Clark, D. E., Zhu, B. F., Hench, L. L., Wicks, G. G. and Werme, L., *An Evaluation of Six-Month Burial Data from Stripa*, *Rivista della Stes. Sper. Vetro.* n5, pp. 185-195 (1984).
- [10] Zhu, B. F., Clark, D. E., Hench, L. L., Wicks, G. G. and Werme, L., *One-Year Leaching of Three SRL Glasses in Granite*, Scientific Basis for Nuclear Waste Management VIII, Materials Research Society, C. M. Jantzen, J. A. Stone and R. C. Ewing eds., Vol. 44, pp. 187-194 (1985).
- [11] Zhu, B. F., Clark, D. E., Hench, L. L., Wicks, G. G. and Werme, L., *Leaching Behavior of Nuclear Waste Glass Heterogeneities*, presented at the 1984 International Symposium on Glass in Beijing, also *J. Non-Crystalline Solids*, Vol. 80, pp. 324-334 (1986).
- [12] Lodding, A., Engstrom, E. U., Clark, D. E., Werme, L. O. and Wicks, G. G., *SIMS Analysis of Leached Layers Formed on SRL Glasses During Burial*, Nuclear Waste Management II, Advances in Ceramics, American Ceramic Society, D. E. Clark, W. B. White and A. J. Machiels eds., Vol. 20, pp. 567-581 (1987).
- [13] Zhu, B. F., Clark, D. E., Lodding, A. and Wicks, G. G., *Two-Year Leaching Behavior of Three SRL Nuclear Waste Glasses in Granite*, Nuclear Waste Management II, Advances in Ceramics, American Ceramic Society, D. E. Clark, W. B. White and A. J. Machiels eds., Vol. 20, pp. 591-599 (1987).
- [14] Wicks, G. G., Weinle, M. E. and Molecke, M. A., *WIPP/SRL In-Situ Tests - Part II: Pictorial History of MIIT and Final MIIT Matrices, Assemblies and Sample Listings*, DP-1733, Savannah River Laboratory, Aiken, SC (1987).

- [15] Wicks, G. G. and Molecke, M. A., *WIPP/SRL In-Situ Testing Program, Nuclear Waste Management II*, Advances in Ceramics, American Ceramic Society, D. E. Clark, W. B. White and A. J. Machiels eds., Vol. 20, pp. 65-667 (1987).
- [16] Wicks, G. G. and Molecke, M. A., *WIPP/SRL In-Situ Testing Program - An April 1987 Update*, DP-MS-87-4, Savannah River Laboratory, Aiken, SC (1987).
- [17] Molecke, M. A. and Wicks, G. G., *Test Plan: WIPP Materials Interface Interactions Test [MIIT]*, Sandia National Laboratories, Albuquerque, NM (1986).
- [18] Newton, R. G., *Summary of the Progress of the Ballidon Glass Burial Experiment*, Glass Technology, 22, No. 1 (1981).
- [19] Newton, R. G., *Ballidon Glass Burial Experiment*, Glass Technology, 26, No. 6 (1985).
- [20] Wicks, G. G., Jantzen, C. M. and Plodinec, M. J., *SRL In-Situ Tests in the United Kingdom - Part I: Program Document and Sample Emplacements*, DPST-88-494, Savannah River Laboratory, Aiken, SC (1988).
- [21] Mellinger, G. B. and Daniel, J. L., *Approved Reference and Testing Materials for Use in Nuclear Waste Management Research and Development Programs*, PNL-4955-2, Pacific Northwest Laboratory, Richland, WA (1984).
- [22] Newton, R. G. and Paul, A., *A New Approach to Predicting the Durability of Glasses from their Chemical Compositions*, Glass Technology, 21[6], pp. 307-309 (1980).
- [23] Plodinec, M. J., Jantzen, C. M. and Wicks, G. G., *Thermodynamic Approach to Prediction of the Stability of Proposed Radwaste Glasses*, Advances in Ceramics VIII, G. G. Wicks and W. A. Ross eds., The American Ceramic Society, Columbus OH, pp. 491-495 (1984).
- [24] Plodinec, M. J., Jantzen, C. M. and Wicks, G. G., *Stability of Radioactive Waste Glasses Assessed from Hydration Thermodynamics*, Scientific Basis for Nuclear Waste Management VII, G. L. McVay ed., North-Holland,

NY, pp. 755-762 (1984).

- [25] Jantzen, C. M. and Plodinec, M. J., *Thermodynamic Model of Natural, Medieval, and Nuclear Waste Glass Durability*, J. Non-Crystalline Solids 67, pp. 207-233 (1984).
- [26] Jantzen, C. M., *Prediction of Nuclear Waste Glass Durability from Natural Analogs*, Advances in Ceramics XX, D. E. Clark, W. B. White and A. J. Machiels eds., The American Ceramic Society, Westerville, OH, pp. 703-712 (1986).
- [27] Wicks, G. G., Lodding, A.R., Macedo, P.B., Clark, D.E., and Molecke, M.A., *MIIT: International In-Situ Testing of Simulated HLW Forms- Preliminary Analyses of SRL 165/TDS Waste Glass and Metal Systems*, High Level Radioactive Waste Management, Vol. 1, p. 443 (1990).

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Table 1

Sample Matrix for UK Ballidon Burial Tests

Shape	Samples	Time				Total Sample Inventory
		1 yr	2 yr	5 yr	16 yr	
Pineapple Slices [2.1" x 0.8" x 0.2"]	165/TDS	2	2	2	2	8
	131/35% TDS	1	1	1	1	4
	ARM-1	1	1	1	1	4
	Basalt Glass	1	1	1	1	4
TNX Cores [0.66 x 0.14]	TNX PHP Glass	2	2	2	2	6
	TNX 165/TDS Melter	2	2	2	2	6
Natural Glass Squares [1" x 1" x 1"]	SRL 131	1	1	1	1	2
	Obsidian	1	1	1	1	2
	Pyrex	1	1	1	1	2
	Silica	1	1	1	1	2
	Basalt	1	1	1	1	2
	Frit 131	1	1	1	1	2
	BF 165	1	1	1	1	2

☐ Denotes current study

Table 2

GLASS COMPOSITIONS [Wt. %] for Ballidon Tests													

Table 3

**CHARACTERIZATION OF 1 & 2 YEAR
BALLIDON SAMPLES (Pineapple Slices)**
(SEM, XES, WAXD and SIMS Analyses)

SAMPLES	ONE YEAR				TWO YEARS		
	SEM/XES		SIMS	WAXD	SEM/XES		WAXD
	Avg. Ppt. Layer (α)	Interaction Zone (β)	Interaction Zone (β)	Structure /Phases	Avg. Ppt. Layer (α)	Interaction Zone (β)	Structure /Phases
165/TDS	$\sim 2\mu$	$< 1\mu$	0.2μ	Glassy	$\sim 2\mu$	$< 1\mu$	Magnesium Manganese Iron Silicate Hydroxide Silicon Oxide Calcium Carbonate
131/35% TDS	$\sim 2\mu$	$< 1\mu$	0.6μ	Glassy	$\sim 2\mu$	$< 1\mu$	Magnesium Manganese Iron Silicate Hydroxide Silicon Oxide Calcium Carbonate
ARM-1	$\sim 2\mu$	$< 1\mu$	0.6μ	Glassy	$\sim 2\mu$	$< 1\mu$	Magnesium Manganese Iron Silicate Hydroxide Silicon Oxide Calcium Carbonate
Basalt			0.06μ	Glassy	$\sim 2\mu$	$< 1\mu$	Calcium Silicate Magnesium Iron Oxide

Figure 1
Sample Configurations for Ballidon Study

A. TNX Core Specimens

B. Natural Glass Cubes

C. Pineapple Slices

Figure 2

PHOTOGRAPH & SCHEMATIC REPRESENTATION OF FOUR BURIAL LOCATIONS CONTAINING SRL GLASSES

Figure 3

CGN
8-10-90

SRL In-Situ Tests in Ballidon, United Kingdom

One-Year Specimen Analysis Matrix

Composition	Specimen Number	Analytical Techniques				
		WAXD	Surface SEM/XES	X-Section SEM/XES	SIMS	FTIRRS
165/TDS	1154	●	●	●	●	○
131/35% TDS	601	●	●	●	●	○
ARM-1	542	●	●	●	●	○
Basalt Glass	673	●			●	○

Two-year Specimen Analysis Matrix

Composition	Specimen Number	Analytical Techniques				
		WAXD	Surface SEM/XES	X-Section SEM/XES	SIMS	FTIRRS
165/TDS	1160	●	●	●	○	○
131/35% TDS	565	●	●	●	○	○
ARM-1	525	●	●	●	○	○
Basalt Glass	689	●	●	●	○	○

NOTES: • The geology at Ballidon in which these samples were buried consists of primarily limestone.

• The samples were buried at ambient conditions approximately 43 inches beneath the surface.

KEY: ○ TO BE PERFORMED
● COMPLETED

Figure 4
Deposits on One-Year Ballidon Samples

Figure 5
SEM/XES, & WAXD Analyses; 165/TDS Waste Glass, 1 Yr.

Figure 6

SEM/XES, & WAXD Analyses; 131/35%TDS Waste Glass, 1 Yr.

Figure 7

SEM/XES, & WAXD Analyses; ARM Reference Glass, 1 Yr.

Figure 8

SIMS Analysis; 165/TDS Waste Glass, 1 Yr.

Figure 9

SIMS Analysis; 131/35%TDS Waste Glass, 1 Yr.

Figure 10
SIMS Analysis; Arm Reference Glass, 1 Yr.

Figure 11
SIMS Analysis; Basalt Glass, 1 Yr.

Figure 12
Deposits on Two-Year Ballidon Samples

Figure 13
SEM/XES, & WAXD Analyses; 165/TDS Waste Glass, 2 Yrs.

SEM/XES, & WAXD Analyses; 165/35%TDS Waste Glass, 2 Yrs.

Figure 15
SEM/XES, & WAXD Analyses; ARM Reference Glass, 2 Yrs.

Figure 16
SEM/XES, & WAXD Analyses; Basalt Glass, 2 Yrs.

SCHEMATIC REPRESENTATION OF PRECIPITATED and LEACHED LAYERS; SRL WASTE GLASSES IN LIMESTONE

[BALLIDON, UNITED KINGDOM]

Figure 17

END

**DATE
FILMED**

4 / 23 / 92