**Integration and Testing of Hot Desulfurization and
Entrained-Flow Gasification for Power Generation Systems,
Phase II, Process Optimization, Volume III -- Effect/Fate of
Chlorides in the Zinc Titanate Hot-Gas Desulfurization Process**

Topical Report

**S.K. Gangwal
T.M. Paar
W.J. McMichael**

Work Performed Under Contract No.: DE-FC21-87MC23277

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Texaco Inc.
Montebello Research Laboratory
P.O. Box 400
Montebello, California 90640**

September 1991

TABLE OF CONTENTS

Section	Page
1.0 Objectives and Background	1
2.0 Experimental	1
2.1 TGR Apparatus	2
2.2 General Test Procedure	2
2.3 Test 1	5
2.4 Test 2	6
2.5 Test 3	6
3.0 Results	7
4.0 Discussion	7
4.1 Effect/Fate of Chloride	7
4.2 Zinc and Capacity Loss	12
5.0 Conclusions and Recommendations	18

LIST OF APPENDICES

Appendix A: Test 1 Cycles	A-1
Initial weight fraction corresponds to that at end of previous cycle, with starting weight prior to first cycle normalized to 1	
Appendix B: Test 1 Cycles	B-1
Initial weight normalized to 1 for each cycle	
Appendix C: Test 2 Cycles	C-1
Initial weight fraction corresponds to that at end of previous cycle, with starting weight prior to first cycle normalized to 1	
Appendix D: Test 2 Cycles	D-1
Initial weight normalized to 1 for each cycle	
Appendix E: Test 3 Cycles	E-1
Initial weight fractions corresponding to that at end of previous cycle, with starting weight prior to first cycle normalized to 1	
Appendix F: Test 3 Cycles	F-1
Initial weight normalized to 1 for each cycle	
Appendix G: Sulfur capacity data at saturation and 100 minutes for Tests 1 to 3	G-1

LIST OF FIGURES

Figure 1. RTI Atmospheric Pressure TGR System	3
Figure 2. DuPont 951 Thermogravimetric Analyzer	4
Figure 3. Sorbent Starting Weight as a Function of Cycle Number	10
Figure 4. Sulfur Capacity Versus Cycle No. for Test 1	13
Figure 5. Sulfur Capacity Versus Cycle No. for Test 2	14
Figure 6. Sulfur Capacity Versus Cycle No. for Test 3	15

LIST OF TABLES

Table 1: TGR Gas Compositions (Volume %)	5
Table 2: Explanation of Appendices for TGR Weight-Time Curves	7
Table 3: Sample Weights Loaded and Removed	8
Table 4: Test 1 Samples Sulfur, Zinc and Titanium Analysis	9
Table 5: Chlorine Analysis of Samples From Tests 2 and 3 (ppmv Chloride)	9
Table 6: Calculated TGR Sulfur Capacity Versus Measured Capacity for Test 1 Samples (lb per 100 lb sorbent)	16
Table 7: Zinc to Titanium Elemental Ratio of Fresh and Used Sorbent for Test 1 (L-3196 used for Test 1)	17
Table 8: Zinc Loss for Balance Arm Pellet	18
Table 9: Titanium Loss for Balance Arm Pellet	18

EFFECT/FATE OF CHLORIDES IN THE ZINC TITANATE HOT-GAS DESULFURIZATION PROCESS

1.0 OBJECTIVES AND BACKGROUND

The objective of this project was to support Texaco's effort to develop the zinc titanate hot-gas desulfurization process for gases produced from their oxygen-blown coal gasifier by answering two key questions that had remained unanswered to date. These questions were: Will chloride in the coal gas affect the performance of the sorbent? and Where would the chloride end up following sulfidation and regeneration? Previously, Research Triangle Institute (RTI) completed a bench-scale test series, under a subcontract to Texaco, Inc., for their contract with the U.S. Department of Energy/Morgantown Energy Technology Center (DOE/METC), in which zinc titanate was shown to be a highly promising sorbent for desulfurizing the Texaco O₂-blown simulated coal gas. The next step was to evaluate the effect of coal gas contaminants, particularly chloride, on the sorbent. No tests have been carried out in the past that evaluate the effect of chloride on zinc titanate. If ZnO in the sorbent reacts with the chloride, zinc chloride may form which may evaporate causing accelerated zinc loss. Zinc chloride may revert back to the oxide during oxidative regeneration. This may be enhanced in the presence of steam. This report provides results of a three-test series which was designed to give some definitive answers about the fate of chloride in the hot-gas desulfurization process and the effect of chloride on the performance of zinc titanate.

2.0 EXPERIMENTAL

RTI carried out three 10-cycle thermogravimetric reactor (TGR) tests in this project. The sorbent used for all testing was UCI L-3196 (1.5ZnO·TiO₂). This section is divided into five subsections. In the first subsection, the TGR equipment is described with its unique

capability. A general test procedure is described in the next subsection. This is followed by descriptions of each of the three tests.

2.1 TGR Apparatus

The TGR apparatus used is shown in Figure 1 and a blowup of the DuPont 951 Thermogravimetric Analyzer (TGA) used for the TGR apparatus is shown in Figure 2. The apparatus has the capability to react simulated coal gas or regeneration gas in broad composition and temperature ranges with the sorbent.

Different lines are provided for inert purge, sulfidation gas, clean coal gas, and regeneration gas. Steam at desired concentration is generated by a positive displacement pump used to inject deionized water in a heated test gas manifold. The most unique capabilities of the TGR are (1) true kinetics of single pellet reactions can be measured (with essentially no effect of the pellet holder); this is possible by using a thin open quartz ring as the pellet holder and (2) up to five pellets can be exposed to the same reaction environment; one pellet sits on the ring and the other four sit in the outer quartz tube slightly downstream of the pellet on the ring. The data collected from the TGR are stored by the DuPont 951, transferred to an IBM-PC, converted to a LOTUS 1-2-3 worksheet, and plotted.

2.2 General Test Procedure

Three 10-cycle TGR tests were conducted at atmospheric pressure. One complete cycle was defined as:

- 30-min reductive regeneration at 700 °C,
- 4-h sulfidation at 700 °C, and
- 2.5-h oxidative regeneration at 700 °C.

Each test was conducted with five pellets. One pellet was placed on the quartz ring and four additional pellets were placed in the same reaction environment. All pellets were cut to the same size and weighed approximately 275 mg. Pellets were subjected to either

Figure 1. RTI Atmospheric Pressure TGR System.

Figure 2. DuPont 951 Thermogravimetric Analyzer.

sulfur or chloride (depending on test) measurement according to the following schedule:

- first pellet after fifth sulfidation
- second pellet after fifth oxidative regeneration
- third pellet after sixth reductive regeneration
- fourth pellet after 10th sulfidation
- fifth pellet (on quartz ring) at end of test after 10th oxidative regeneration.

Prior to beginning the designated test series, a few shakedown runs were conducted mimicking the test procedure to make sure all equipment was functioning correctly.

2.3 Test 1

Test 1 was a baseline test without chloride in the gas. The gas compositions used for this test are shown in Table 1. The sulfidation gas simulated the Texaco oxygen-blown gas.

TABLE 1. TGR GAS COMPOSITIONS (VOLUME %)

	Sulfidation Gas	Reductive Regeneration Gas	Oxidative Regeneration Gas
CO	39.10	39.10	--
H ₂	30.13	31.13	--
CO ₂	12.25	12.25	--
H ₂ O	17.52	17.52	--
N ₂	--	--	98.00
H ₂ S	1.00	--	--
O ₂	--	--	2.00

The pellets were removed according to the schedule presented in Subsection 2.2. Each pellet was analyzed for crush strength and total sulfur. All pellets were weighed before and after testing using an analytical balance. This was in addition to the weight-time curves available for each cycle from the TGA.

2.4 Test 2

Test 2 was run at conditions identical to Test 1 with the exception of having 500 ppmv chloride (as HCl) in the sulfidation gas and reductive regeneration gas. The HCl was injected into the gas using an HCl solution in water in place of the water used to regenerate steam. Five hundred ppmv chloride concentration was chosen because it is higher than the upper limit of expected chloride in oxygen-blown coal gas. The test results of chloride effect would thus be representative of tests longer than the test to be conducted. For the 10-cycle test, it is to be noted that the pellet on the balance arm was exposed to chloride along with H₂S for a total of 40 hours and to chloride in the absence of H₂S for 5 hours.

Pellets removed according to the General Test Procedure were weighed and analyzed for crush strength and chloride. This combined with the results of the TGA weight-time curves was expected to provide definitive results of the fate and effect of chloride.

2.5 Test 3

Test 3 was carried out at conditions identical to Test 2 with the exception that oxidative regeneration was carried out with a regeneration gas containing 2% O₂, 48% N₂, and 50% steam. To generate this regeneration gas, the HCl solution was replaced with clear deionized water prior to each oxidative regeneration. As before, pellets removed according to the General Test Procedure were weighed and analyzed for crush strength and chloride. These results combined with the TGA weight-time curves and compared to corresponding results of Tests 1 and 2 were expected to enable conclusions to be drawn regarding the effect of steam during oxidative regeneration when chloride was present in coal gas.

3.0 RESULTS

The TGR weight-time curves are shown in Appendices A to F. The explanation of these appendices is shown in Table 2. Each plot in the appendices represents a full cycle.

**TABLE 2. EXPLANATION OF APPENDICES FOR
TGR WEIGHT-TIME CURVES**

Appendix No.	Test No.	Initial Weight Fraction
A	1	Corresponding to end of previous cycle
B	1	Normalized to 1
C	2	Corresponding to end of previous cycle
D	2	Normalized to 1
E	3	Corresponding to end of previous cycle
F	3	Normalized to 1

The sample weights loaded and removed are shown in Table 3. The crush strengths of the used samples are also shown in this table. The total sulfur, zinc, and titanium analyses of Test 1 pellets are shown in Table 4 and the chlorine analyses of Test 1 and Test 3 are shown in Table 5.

4.0 DISCUSSION

4.1 Effect/Fate of Chloride

Upon comparing the TGR results of Test 1 with Test 2 (Appendices A and B versus C and D, and Table 3), it may be concluded that chloride at the 500 ppm level in Texaco gas has no adverse effect on sorbent sulfur capacity and crush strength. The weight loss of the sorbent due to zinc evaporation is identical for both tests (Figure 3).

TABLE 3. SAMPLE WEIGHTS LOADED AND REMOVED

Test No.	Pellets in (mg)	Pellets out (mg)	% Weight Change	Crush Strength lb/mm	Removal Point
1	275.71	291.38	+5.7	4.8	After fifth sulfidation
	268.77	259.74	-3.4	5.2	After fifth oxidative regeneration
	279.02	268.07	-3.9	4.7	After sixth reductive regeneration
	273.70	272.98	-0.3	4.7	After tenth sulfidation
	279.95	249.56	-10.9	4.2	After tenth oxidative regeneration
2	278.03	295.65	+6.0	4.8	After fifth sulfidation
	275.42	266.03	-3.4	4.5	After fifth oxidative regeneration
	275.13	264.44	-3.9	5.8	After sixth reductive regeneration
	272.93	273.30	+0.1	4.2	After tenth sulfidation
	275.60	246.43	-10.6	4.8	After tenth oxidative regeneration
3	278.37	288.78	+3.7	4.3	After fifth sulfidation
	275.75	263.62	-4.7	4.3	After fifth oxidative regeneration
	273.78	259.08	-5.4	5.5	After sixth reductive regeneration
	270.56	267.38	-1.2	4.2	After tenth sulfidation
	281.08	241.53	-14.1	3.8	After tenth oxidative regeneration

TABLE 4. TEST 1 SAMPLES SULFUR, ZINC AND TITANIUM ANALYSIS

Removal Point	Total Sulfur (Weight %)	Zinc (Weight %)	Titanium (Weight %)
After fifth sulfidation	17.00	40.2	22.7
After fifth oxidative regeneration	0.42	45.8	24.2
After sixth reductive regeneration	0.23	45.0	24.2
After tenth sulfidation	16.5	38.0	23.2
After tenth oxidative regeneration	0.22	42.6	25.4
Fresh L-3196	--	44.9	23.4
Fresh L-3014	--	34.4	31.0

**TABLE 5. CHLORINE ANALYSIS OF SAMPLES FROM
TESTS 2 AND 3 (ppmv Chloride)**

Removal Point	Test 2	Test 3
After fifth sulfidation	83	8100
After fifth oxidative regeneration	31	<18
After sixth reductive regeneration	665	519
After tenth sulfidation	576	243
After tenth oxidative regeneration	<19	<19

1.5 ZnO.TiO₂ Weight Loss

Figure 3. Sorbent Starting Weight as a Function of Cycle Number.

Upon comparing the TGR results of Tests 1 and 3 (Appendices A and B versus E and F, and Table 3), the weight loss of the sorbent (presumably due to zinc evaporation) is about 30% greater for Test 3 (Figure 3). It is not clear to us why the inclusion of steam in the regeneration gas resulted in increased weight loss of the sorbent. It is possible that chloride captured by the zinc during sulfidation was more easily removed during regeneration in the presence of steam and this caused a greater zinc loss. Another explanation is temperature differences during sulfidation. The TGR thermocouple does not touch the sorbent because its weight needs to be measured continuously. Since the sulfidations were run identically for all these tests, this second explanation is less likely than the first. The crush strengths of samples from Test 3, however, were not different from those of Tests 1 and 2.

Based on the above, we may conclude that chloride had no adverse effect on the sorbent when N₂ only was used as the regeneration diluent. When 50% steam was used in the regeneration gas, the zinc loss was about 30% greater. In order to determine the fate of chloride, samples were analyzed as shown in Table 5. The results are consistent except for the high chloride in one sample for Test 3 (0.81% after fifth sulfidation). We have no definite explanation of this chloride value. An inadvertent surge of liquid at lower temperature may have caused this or this may be an analytical error. Unfortunately, all of the sample was used up for the analysis and thus the more likely cause cannot be pinpointed.

The maximum chloride level in the sorbent is about 665 ppmv. As regeneration appears to remove the chloride, chloride may end up in the regeneration off-gas and its effect on downstream processing must be assessed.

At sulfidation No. 5, Test 2, the chloride level was only 83 ppmv. But after the tenth sulfidation, the chloride level was about seven times higher (576 ppmv). This is probably due to the fact that the sorbent became reactive with cycles (presumably due to increase in internal accessibility from zinc evaporation). H_2S and HCl apparently compete for zinc. Both reactions appear approximately first order based on the tenth sulfidation, considering that we had 1% (10,000 ppmv) H_2S versus only 500 ppmv HCl in the feed. Thus zinc captured by chloride versus sulfide is approximately proportional to the respective chloride and sulfide levels in the gas.

4.2 Zinc and Capacity Loss

Although not originally of concern in this project, it was found that a significant portion of the zinc was lost from the sorbent mainly due to the high temperature of operation. To assess the impact of this loss on the capacity, the data were analyzed. The data for sulfur capacity versus cycle for the three tests are shown in Appendix G. A saturation capacity and a 100-min capacity are tabulated. As seen, although the saturation capacity decreases with cycles, the 100-min capacity remains essentially constant or increases. This is due to the significant increase in sorbent reactivity as seen by the fact that the sulfidations and regenerations become faster as cycles progress (Appendices A to B). The data from Appendix G are plotted in Figures 4 to 6 for Tests 1 to 3, respectively. The increase in the 100-min capacity could result in an increase in sorbent utilization up to a certain number of cycles. However, as zinc continues to be lost, the utilization must also begin to drop. This did not happen after 10 cycles but must eventually happen. A longer test needs to be run to determine when the trend would be reversed.

TEST 1

Figure 4. Sulfur Capacity Versus Cycle No. for Test 1.

TEST 2

Figure 5. Sulfur Capacity Versus Cycle No. for Test 2.

TEST 3

Figure 6. Sulfur Capacity Versus Cycle No for Test 3.

The measured saturation capacity (TGA) is compared to actual Leco sulfur measurement for Test 1 in Table 6. The loss in capacity as measured by Leco is somewhat less than that calculated based on TGA results.

TABLE 6. CALCULATED TGR SULFUR CAPACITY VERSUS MEASURED CAPACITY FOR TEST 1 SAMPLES (lb per 100 lb sorbent)

Sample	TGR	Measured by LECO
After fifth sulfidation	19.2	18.0
After tenth sulfidation	15.2	16.5

The sorbent zinc and titanium measurements were also carried out using flame atomic absorption spectroscopy for zinc and inductively coupled plasma spectroscopy for titanium. The zinc to titanium elemental ratio calculated using Table 4 is shown in Table 7.

The reduction in Zn/Ti elemental ratio does not appear to be significant over five cycles but becomes more pronounced between cycles 5 and 10 as seen from Table 7. Although, as would be expected, some scatter in data exists possibly due to pellet to pellet variations, the trend is definitely downwards. One important question to answer is when will the ratio stabilize, if at all? Also, should one start with a sorbent with Zn/Ti ratio of 0.8 to 1.0 to avoid this trend or should one operate at somewhat lower temperatures during sulfidation?

The loss of zinc for the balance arm pellet is shown in Table 8. The corresponding zinc oxide loss is 24.15 mg. The additional loss (i.e., $30.3 - 24.15 = 6.15$ mg) may be

attributed to binder, titanium or oxygen or a combination. We began with 3% binder (i.e., 8.4 mg). The titanium balance is shown in Table 9.

The loss of titanium may have shown up due to an analytical error. In any event, the loss is much less significant than zinc.

TABLE 7. ZINC TO TITANIUM ELEMENTAL RATIO OF FRESH AND USED SORBENT FOR TEST 1 (L-3196 used for Test 1)

	Nominal	Measured	% Reduction in Ratio
L-3196	1.5	1.41*	--
After fifth sulfidation	--	1.30	7.8
After fifth oxidation	--	1.39	1.42
After sixth reduction	--	1.36	3.54
After tenth reduction	--	1.20	14.9
After tenth oxidation	--	1.23	12.1
L-3014	0.8	0.81	--

* Analysis of a sample produced by crushing and homogenizing 20 pellets. The other analyses are based on single pellet

TABLE 8. ZINC LOSS FOR BALANCE ARM PELLET

	Pellet Weight	Weight % Zn	Zinc (mg)
Fresh	279.95	44.9	125.7
Used	249.56	42.6	106.3
(10 cycles)			
	Weight loss = 30.39 mg Zinc loss = 19.4 mg (15.4%)		
	Zinc Oxide Loss = $\frac{19.4 \times 81.38}{65.38} = 24.15 \text{ mg}$		

TABLE 9. TITANIUM LOSS FOR BALANCE ARM PELLET

	Pellet Weight	Weight % Zn	Zinc (mg)
Fresh	279.95	23.4	65.51 mg
Used	249.56	25.4	63.39 mg
(10 cycles)			
	Titanium loss = 19.4 mg (15.4%)		
	Titanium Dioxide Loss = $\frac{2.12 \times 79.9}{47.9} = 3.54 \text{ mg}$		

5.0 CONCLUSIONS AND RECOMMENDATIONS

Based on the study, the following conclusions and recommendations are made:

- 500 ppmv of chloride does not appear to have a deleterious effect on capacity over 10 cycles for zinc titanate at 700 °C in the presence of Texaco O₂-blown syn-gas.
- Sorbent regeneration removes residual chloride, thus much of the chloride may appear in the regeneration off-gas.

- The crush strength of the sorbent is not affected at 700 °C by chloride.
- Significant zinc loss occurs from the L-3196 sorbent over 10 cycles at 700 °C. The Zn to Ti elemental ratio drops from about 1.4 to 1.2.
- The sorbent becomes significantly more reactive with cycles presumably caused by opening of porous structure due to zinc evaporation. This results in greater effective utilization over 10 cycles in spite of zinc loss.
- The zinc loss is about 30% greater over 10 cycles when the regeneration gas contain 50% steam versus when it contains no steam.
- Further tests should be conducted to define the zinc loss better. Some recommendations in this regard include:
 - (1) a 10-cycle test with 0.8 or 1.0 zinc titanate at 700 °C,
 - (2) a 10-cycle test with a selected zinc titanate at 650 °C. Zinc titanate to be selected on the basis of results for (1), and
 - (3) a 30-cycle test with a selected zinc titanate at a selected temperature based on results of (1) and (2).

Appendix A

TEST 1 CYCLES

**Initial weight fraction corresponds to that
at end of previous cycle, with starting
weight prior to first cycle normalized to 1**

TEST 1-CYCLE 1

TEST 1-CYCLE 2

TEST 1-CYCLE 3

TEST 1-CYCLE 4

TEST 1-CYCLE 5

TEST 1-CYCLE 6

TEST 1-CYCLE 7

TEST 1-CYCLE 8

TEST 1-CYCLE 9

TEST 1-CYCLE 10

Appendix B

TEST 1 CYCLES

**Initial weight normalized to 1 for each
cycle**

TEST 1-CYCLE 1

TEST 1-CYCLE 2

TEST 1 - CYCLE 3

TEST 1 - CYCLE 4

TEST 1-CYCLE 5

TEST 1-CYCLE 6

TEST 1-CYCLE 7

TEST 1-CYCLE 8

TEST 1-CYCLE 9

TEST 1-CYCLE 10

Appendix C

TEST 2 CYCLES

**Initial weight fraction corresponds to that
at end of previous cycle, with starting
weight prior to first cycle normalized to 1**

TEST 2-CYCLE 1

TEST 2--CYCLE 2

TEST 2-CYCLE 3

TEST 2-CYCLE 4

TEST 2-CYCLE 5

TEST 2-CYCLE 6

TEST 2-CYCLE 7

TEST 2-CYCLE 8

TEST 2-CYCLE 9

TEST 2-CYCLE 10

Appendix D

TEST 2 CYCLES

**Initial weight normalized to 1 for each
cycle**

TEST 2--CYCLE 1

TEST 2-CYCLE 2

TEST 2-CYCLE 3

TEST 2-CYCLE 4

TEST 2-CYCLE 5

TEST 2-CYCLE 6

TEST 2-CYCLE 7

TEST 2-CYCLE 8

TEST 2-CYCLE 9

TEST 2-CYCLE 10

Appendix E

TEST 3 CYCLES

**Initial weight fractions corresponding to
that at end of previous cycle, with starting
weight prior to first cycle normalized to 1**

TEST 3-CYCLE 1

TEST 3-CYCLE 2

TEST 3-CYCLE 3

TEST 3-CYCLE 4

TEST 3-CYCLE 5

TEST 3-CYCLE 6

TEST 3-CYCLE 7

TEST 3-CYCLE 8

TEST 3-CYCLE 9

TEST 3-CYCLE 10

Appendix F

TEST 3 CYCLES

**Initial weight normalized to 1 for each
cycle**

TEST 3-CYCLE 1

TEST 3-CYCLE 2

TEST 3-CYCLE 3

TEST 3-CYCLE 4

TEST 3-CYCLE 5

TEST 3-CYCLE 6

TEST 3-CYCLE 7

TEST 3-CYCLE 8

TEST 3-CYCLE 9

TEST 3-CYCLE 10

Appendix G

**Sulfur capacity data at saturation and 100
minutes for Tests 1 to 3**

TEST 1

INITIAL METTLER WEIGHT = 279.95 mg

CYCLE NO.	WEIGHT INCREASE (AT SATURATION)	LB SULFUR per 100 LB SORBENT	WEIGHT INCREASE (AT 100 MINUTES)	LB SULFUR per 100 LB SORBENT
1	29.43	20.98590	16.347	11.65669
2	27.465	19.58470	14.405	10.27189
3	27.018	19.26596	14.237	10.15210
4	26.909	19.18823	14.5	10.33964
5	26.958	19.22317	14.975	10.67835
6	23.777	16.95487	15.15	10.80314
7	18.493	13.18696	12.562	8.957695
8	20.917	14.91546	16.343	11.65384
9	21.457	15.30053	17.613	12.55945
10	21.258	15.15862	17.739	12.64930

TEST 2

INITIAL METTLER WEIGHT = 275.60 mg

CYCLE NO.	WEIGHT INCREASE (AT SATURATION)	LB SULFUR per 100 LB SORBENT	WEIGHT INCREASE (AT 100 MINUTES)	LB SULFUR per 100 LB SORBENT
1	27.3	19.77431	14.684	10.78098
2	26.659	19.31001	15.038	10.89253
3	26.922	19.50051	13.644	9.882810
4	26.616	19.27886	13.937	10.09504
5	24.22	17.54336	12.022	8.707941
6	24.951	18.07285	14.775	10.70203
7	21.89	15.85566	15.67	11.35031
8	20.818	15.07918	17.144	12.41797
9	20.19	14.62429	18.815	13.62834
10	19.897	14.41207	18.723	13.56170

TEST 3

INITIAL METTLER WEIGHT = 281.08 mg

CYCLE NO.	WEIGHT INCREASE (AT SATURATION)	LB SULFUR per 100 LB SORBENT	WEIGHT INCREASE (AT 100 MINUTES)	LB SULFUR per 100 LB SORBENT
1	27.839	19.77159	13.389	9.509029
2	27.263	19.36251	17.11	12.15172
3	23.883	16.96199	14.836	10.53670
4	24.22	17.20133	17.766	12.61762
5	24.285	17.24749	17.183	12.20357
6	21.619	15.35407	18.188	12.91733
7	20.413	14.49755	18.105	12.85838
8	20.65	14.66587	19.263	13.68081
9	19.217	13.64814	19.245	13.66803
10	19.758	14.03236	19.669	13.96916

END

**DATE
FILMED**

4 / 13 / 93