2
EG&G - NE -10083

APR 27 1992

**Idaho
National
Engineering
Laboratory**

*Managed
by the U.S.
Department
of Energy*

INFORMAL REPORT

EMISSIVITY MEASUREMENTS IN SUPPORT OF
EXPERIMENTS ON NATURAL CONVECTION BETWEEN A
VERTICAL CYLINDER AND A SURROUNDING ARRAY

J. E. O'BRIEN

*Work performed under
DOE Contract
No. DE-AC07-76ID01570*

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

This document contains new concepts or the author(s) interpretation of new calculations and/or measurements; accordingly, EG&G Idaho, Inc. is required by the United States Government to include the following disclaimer:

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

EGG-NE--10083

DE92 012321

**Emissivity Measurements in Support of Experiments on Natural
Convection between a Vertical Cylinder and a Surrounding Array**

J. E. O'Brien

December, 1991

Idaho National Engineering Laboratory
EG&G Idaho, Inc.
P. O. Box 1625
Idaho Falls, ID 83415

prepared for the
U. S. Department of Energy
Idaho Operations Office
under DOE Contract no. DE-AC07-76ID01570

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

ABSTRACT

Experimental measurements of surface emissivities of three metallic samples have been obtained in support of an experiment aimed at determining natural convection and total heat transfer for a heated vertical cylinder surrounded by an array of cooled vertical tubes. In some cases, the heated stainless steel cylinder was shrouded by a perforated aluminum outer cylinder. The surrounding cooled tubes were also aluminum. In this experiment, heat transfer from the heated tube and the surrounding outer cylinder will occur by a combination of natural convection and radiation. At temperatures near the melting point of aluminum, the radiant contribution is particularly important, accounting for 50% or more of the total heat transfer. Consequently, accurate knowledge of surface emissivities of the heated rods, outer cylinders and surrounding structures is needed in order to predict the system thermal response during the transient. Direct measurements of surface emissivities have been obtained for one stainless steel and two aluminum samples. The measurements were obtained using an infrared pyrometer sensitive to the 8-14 μm wavelength range. A procedure for estimating total hemispherical emissivities based on the measured spectral, normal results is also provided.

CONTENTS

ABSTRACT.....	ii
NOMENCLATURE.....	iv
1. INTRODUCTION.....	1
2. APPARATUS AND PROCEDURE.....	2
2.1 Samples.....	2
2.2 Instrumentation.....	2
2.3 Data Reduction.....	3
3. RESULTS.....	6
3.1 Normal Spectral Measurements.....	6
3.2 Relation to Hemispherical Emissivities.....	7
3.3 Estimates of Total, Hemispherical Emissivity.....	8
4. SUMMARY.....	10
5. REFERENCES.....	11
APPENDIX A - Infrared Pyrometer Characteristics and Specifications.....	A1
APPENDIX B - Mathematica algorithms for calculating emissivities and uncertainties.....	B1

FIGURES

1. Schematic of emissivity measurement set-up.....	12
2. Comparison of predicted pyrometer response temperatures to indicated pyrometer temperatures for various emissivity settings.....	13
3. Normal emissivities of stainless steel tube.....	14
4. Normal spectral emissivities of stainless steel (304), from reference [1].....	15
5. Normal emissivities of aluminum samples.....	16
6. Normal spectral emissivities for polished aluminum from reference [1].....	17
7. Relationship between normal and hemispherical emissivities for metals, from [2].....	18
8. Best estimates of total hemispherical emissivities for all samples.....	19
A.1 Infrared pyrometer characteristics.....	20

TABLES

1. Representative emissivity uncertainty values.....	6
2. Ratio of hemispherical to normal emissivity for metallic surfaces.....	8
3. Estimates of total hemispherical emissivities for each sample.....	10

NOMENCLATURE

A_1	surface area of measurement spot, m^2
A_2	surface area of pyrometer aperture, m^2
$E_{\lambda, b}$	spectral blackbody emissive power, $W/m^2 \mu m$
F	fraction of blackbody radiation in a specified wavelength range
n	refractive index
q_i	incident radiant heat flux, W/m^2
r_e	electrical resistivity, Ohm cm
R	distance between radiant source and pyrometer, m
T	temperature, K
T_a	mean radiant temperature of surroundings, K
T_s	surface temperature, K
ϵ	emissivity
ϵ_n	normal total emissivity
$\epsilon_{n, \lambda}$	normal spectral emissivity
$\epsilon_{t, h}$	total hemispherical emissivity
$\delta\epsilon$	estimated emissivity uncertainty
κ	extinction coefficient
λ	wavelength, μm
σ	Stefan-Boltzmann constant, $5.67 \times 10^{-8} W/m^2 K^4$

1. INTRODUCTION

A number of nuclear reactors have core geometries consisting of tall, slender arrays of vertical circular tubes. Several types of tubes are present in these arrays including cooling tubes, fuel rods, control rods, and safety rods. During certain hypothesized loss-of-coolant or loss-of-flow scenarios in water reactors, the core may be partially filled with air or another gas. In this case, any thermal energy being dissipated in the tubes is transferred to the surroundings by a combination of natural convection and radiation. Data for natural convection in these complex geometries are sparse or nonexistent. Work described in this report was performed in support of an effort to obtain natural convection and total heat transfer measurements in a geometry corresponding to a single gamma-heated safety rod surrounded by an array of cooling tubes. The safety rod may or may not be surrounded by a perforated aluminum outer cylinder, referred to as a "thimble."

This situation was simulated experimentally using electrical heating of a "safety rod" assembly surrounded by three aluminum cooling tubes in a tall vertical enclosure bounded by a plexiglas shroud. The experiments were carried out in three phases. In the first phase, a stainless steel safety rod was heated alone with no aluminum thimble in place. In the second and third phases, the thimble was in place. The primary objective of the experiment was to provide data which will help to determine the maximum power dissipation level that can be maintained in the safety rod assembly without a catastrophic thermal failure of the thimble. Since the experiment is not exactly prototypical, this power level determination cannot be measured directly. Rather, careful analysis of the experimental data will provide information on overall heat transfer rates and on the relative contributions of convective and radiative heat transfer, allowing for more accurate general prediction of prototypical heat transfer rates for a variety of scenarios.

In order to address the issue of the relative contributions of radiation and natural convection, measurements of surface emissivities of the stainless steel safety rod material, the aluminum thimble material, and the aluminum cooling tubes were undertaken. At temperatures near the melting point of aluminum, the radiant contribution is particularly important, accounting for 50% or more of the total heat transfer. Although considerable information on emissivities of various materials is available in the literature [e.g., 1-4], there is such a high degree of variability in the data, depending on surface condition and extent of oxidation, for example, that selection of a value from these data bases inevitably involves a level of uncertainty that may be unacceptable for situations in which radiation is important. Direct emissivity measurements of actual components, if feasible, is preferable.

The scope of the project described herein was to obtain direct measurements of surface emissivities for one stainless steel and two aluminum samples taken from the same materials to be used in the experiments. A description of the measurement and data reduction techniques is given, followed by presentation of results. A procedure for estimating total hemispherical emissivities based on the measured spectral, normal results is also provided.

2. APPARATUS AND PROCEDURE

2.1 Samples

Three samples were provided for emissivity measurements. The first sample was a 0.94" OD cylindrical 304 stainless steel safety rod sample identical to the safety rod to be used in the experimental apparatus. The second sample was an aluminum (6063) cylinder identical to the thimble material to be used in the experiments. The third sample was an etched 4" OD aluminum cooling tube. With the exception of the etched cooling tube, each sample was cleaned lightly with isopropyl alcohol before measurements were obtained.

2.2 Instrumentation

Emissivities were measured using an infrared pyrometer (Omega model OS-2104 L) designed primarily for measuring temperatures of radiating surfaces. Specifications of this pyrometer are attached to this report as appendix A. The pyrometer features a digital emissivity readout which allows the user to input the estimated emissivity of the radiating surface so that a reasonable estimate of the surface temperature can be made. Conversely, if the surface temperature is known independently, surface emissivity can be measured by adjusting the emissivity input value until the indicated pyrometer temperature matches the known surface temperature. One important specification of the pyrometer used in this study is its wavelength range of sensitivity, which is 8 - 14 μm . Therefore, the emissivities measured in this study are normal spectral emissivities averaged over the wavelength range of 8 - 14 μm . The measurement spot size for the pyrometer is 0.25 in. diameter when the pyrometer aperture is located 2 ft. from the radiating surface.

A schematic of the emissivity measurement setup used for these tests is shown in Fig. 1. Cylindrical samples were heated internally using commercially available cartridge heaters (Watlow firerod heaters). An on/off temperature controller (Omega model 4001KF) was used to maintain a constant sample temperature during the measurement period at each temperature set point.

Sample surface temperatures were monitored using four type K thermocouples spot welded to the sample surface in the pattern shown in Fig. 1. The representative surface temperature at the measurement spot was taken to be the average of the four thermocouple readings. For the safety rod and thimble samples, the gap between the outer diameter of the cartridge heater and the inner diameter of the sample was occupied by a boron nitride insert machined to fit the required dimensions with a minimum clearance gap. Boron nitride was chosen for this application due to its ability to withstand high temperatures, its high thermal conductivity, and its very low thermal expansion coefficient. An aluminum insert machined from aluminum bar stock was used in place of a boron nitride inser for heating the cooling tube sample.

Room air temperature was monitored continuously during the emissivity measurements using a precision RTD thermometer. This temperature was assumed to represent the laboratory mean radiant temperature, T_a . The pyrometer has an internal temperature sensor (at or very close to room air temperature) which the microprocessor treats as the appropriate T_a value unless the alternate T_a mode is activated.

The procedure for obtaining emissivity measurements consisted of heating the sample to the desired temperature, locating the pyrometer aperture exactly 2 ft. from the measurement spot in the normal direction, aiming the pyrometer at the measurement spot using the built-in HeNe pointing laser permanently mounted on the pyrometer, and activating the pyrometer. The emissivity setting on the pyrometer was varied until the indicated pyrometer temperature matched the known surface temperature. In measurement situations involving emissivity values lower than 0.1, the pyrometer emissivity value was set to 0.1 (the lowest available setting) and the indicated temperature was recorded corresponding to an emissivity of 0.1. The actual emissivity value was obtained for these cases from the post-test data reduction procedure described below.

2.3 Data Reduction

The quantity actually measured by the thermopile detector in the pyrometer is that portion of the incident radiant flux (emission plus reflection from the target surface) entering the primary aperture of the focusing optics which is imaged on the thermopile and which is in the wavelength band of sensitivity of the pyrometer. Incident radiation is filtered such that the wavelength band of sensitivity is limited. An expression for this incident flux is

$$q_{i, \lambda} = \frac{A_1 A_2}{\pi R^2} (E_{e, \lambda} + G_{ref, \lambda}) \quad (1)$$

where the sum in parentheses represents emission plus reflection from the target surface in the pyrometer wavelength band of sensitivity and the multiplying ratio is the constant geometric extent. Substituting appropriate expressions for emitted and reflected radiant fluxes and noting that the wavelength band set by the filter used in this study was 8 - 14 μm ,

$$q_{(i, 8-14 \mu\text{m})} = \frac{A_1 A_2}{\pi R^2} [\epsilon \sigma T_s^4 F(T_s, 8-14 \mu\text{m}) + (1-\epsilon) \sigma T_a^4 F(T_a, 8-14 \mu\text{m})] \quad (2)$$

where the $F(T, \lambda)$ quantities represent the fraction of graybody radiation in the pyrometer wavelength band of sensitivity at temperature T and ϵ is the emissivity of the target surface. A microprocessor is interfaced to the detector. This microprocessor performs the calculation of the temperature of the emitting surface based on the detected radiant flux and two user input quantities: ϵ and T_a . The first quantity, ϵ , is the emissivity of the emitting/reflecting target surface. The second quantity, T_a , is the mean radiant temperature of the surroundings adjacent to the target surface. The equation solved by the microprocessor in performing the surface temperature calculation is obtained by rearranging eqn. (2) above, yielding

$$T_s = \left[\frac{q_{(i, 8-14 \mu\text{m})} \left(\frac{\pi R^2}{A_1 A_2} \right) - (1-\epsilon) \sigma T_a^4 F(T_a, 8-14 \mu\text{m})}{\epsilon \sigma F(T_s, 8-14 \mu\text{m})} \right]^{1/4} \quad (3)$$

Solved in terms of emissivity, eqn. (3) becomes:

$$\epsilon = \frac{q_{i, 8-14 \mu\text{m}} \left(\frac{\pi R^2}{A_1 A_2} \right) - \sigma T_a^4 F(T_a, 8-14 \mu\text{m})}{\sigma T_s^4 F(T_s, 8-14 \mu\text{m}) - \sigma T_a^4 F(T_a, 8-14 \mu\text{m})} \quad (4)$$

In order to verify that the pyrometer microprocessor was indeed using eqn. (3) as the governing equation for temperature measurement, an auxiliary experiment was performed in conjunction with the initial pyrometer qualification experiment. During this experiment, a blackbody surface (Omega BB-1) was maintained at a constant elevated temperature and a series of indicated temperature readings was obtained for different values of emissivity input to the pyrometer. Predictions of indicated temperatures were also estimated from eqn. (3) and compared to the indicated temperatures obtained from the pyrometer. Results of this experiment are shown in Fig. 2. The agreement between the predicted temperatures and the indicated temperatures demonstrates that equation (3) serves as the governing equation for the pyrometer. Temperatures predicted without

considering the spectral sensitivity of the pyrometer are also shown in the figure as graybody predicted temperatures.

For surfaces with emissivities lower than 0.1, eqn. (4) was used to calculate the actual surface emissivity from the indicated surface temperature (from the pyrometer) and the actual surface temperature (from the thermocouples). Knowledge of the pyrometer-indicated temperature, the pyrometer emissivity (eg., 0.1), and the mean radiant temperature, T_a , allows for determination of the radiant flux product:

$$q_{i, 8-14 \mu m} \left(\frac{\pi R^2}{A_1 A_2} \right) = \epsilon \sigma T_s^4 F(T_s, 8-14 \mu m) + (1-\epsilon) \sigma T_a^4 F(T_a, 8-14 \mu m) \quad (5)$$

Eqn. (4) is then applied using this value for the radiant flux product and the actual values for surface temperature and the known mean radiant temperature.

Uncertainties in the emissivity measurements were quantified using the uncertainty analysis procedure outlined in [6]. This procedure requires evaluation of the partial derivatives of the dependent variable (ϵ in this case) with respect to the independent variables (T_s , T_a , and q_i). In particular,

$$\delta \epsilon = \left\{ \left(\frac{\partial \epsilon}{\partial q} dq \right)^2 + \left(\frac{\partial \epsilon}{\partial T_a} dT_a \right)^2 + \left(\frac{\partial \epsilon}{\partial T_s} dT_s \right)^2 \right\}^{1/2} \quad (6)$$

The required partial derivatives are obtained in principle directly from eqn. (2). Analytical determination of these derivatives is complicated by the appearance of the F functions in eqn. (4).

This function has the form:

$$F(T, 8-14 \mu m) = \frac{\int_8^{14} E_{\lambda,b} d\lambda}{\sigma T^4} \quad (7)$$

and therefore the partial derivatives of ϵ with respect to temperatures must be evaluated numerically. An algorithm (copy attached as appendix B) for estimating uncertainties was developed using Mathematica [7]. Values for the uncertainties in T_s , T_a , and q_i were obtained from standard thermocouple accuracy specifications and the pyrometer specifications, respectively. Re-

Table 1. Representative emissivity uncertainty estimates.					
$\epsilon \backslash T_s$	300 K	400	500	700	900
0.1	.526	.0175	.00729	.00334	.00246
.2	.4731	.0171	.00814	.00494	.00420
.3	.4248	.0178	.00978	.00690	.00611
.4	.3832	.01949	.0119	.00897	.00807
.5	.3509	.02194	.01426	.0111	.0101

sults of the uncertainty calculations are summarized in Table 1. This table includes typical uncertainty values as a function of ϵ and T_s . Overall uncertainties are most sensitive to changes in sample temperature. Uncertainties are highest for temperatures near room temperature and decrease significantly at higher temperatures.

3. RESULTS

3.1 Normal Spectral Measurements

Emissivity results for the stainless steel safety rod sample are presented in Fig. 3. Prior to heating, this sample had a shiny polished appearance. Measured emissivities for this sample increased slightly with temperature, from a value of 0.11 at 335 K to a value of 0.135 at 850 K. Visual inspection of the sample indicated a surface darkening which became apparent at temperatures above approximately 600 K. Fig. 4 is a reproduction of spectral normal emissivity data for stainless steel (304) from reference [1]. Measured emissivity values for our safety rod sample are consistent with the values presented in Fig. 4 for the "unoxidized" sample in the 8 - 14 μm range. According to [4], total normal emissivities for typical polished stainless steels range from 0.17 to 0.30 over a temperature range from 300 - 1000 K. A value of 0.12 appears to be more representative of the total normal emissivity of the present safety rod sample (and for the sample of Fig.4) at 300 K since the peak emission wavelength at 300 K is in the middle of our measurement range of sensitivity (8 - 14 μm).

Emissivity results for the aluminum samples are presented in Fig. 5. Measured thimble emissivities dropped from 0.11 to 0.08 over a temperature range from 350 K to 720 K. Results for the

cooling tube exhibited a similar but more drastic downward trend with temperature from 0.11 at 340 K to 0.061 at 480 K. The explanation for the apparent drop in measured emissivities of these samples with increasing temperature is unknown. For the cooling tube, low-temperature emissivity values were remeasured and duplicated on the second and third heatings, indicating consistency in the measurements and data reduction procedure. These near-room-temperature measurements have a high degree of uncertainty, especially for low values of emissivity, due primarily to extreme sensitivity to the mean radiant temperature, T_a , of the surroundings. For a surface temperature of 350 K and a measured emissivity of 0.1, uncertainty in T_a of only 1° C results in uncertainty in emissivity of ± 0.013 , which is 13% of the measured value.

Spectral normal emissivities of "polished" aluminum samples from reference [1] are presented in Fig. 6. Note that there is also a slight drop in the 8-14 μm average emissivity for these samples between 599 K and 697 K. These samples were maintained at their respective temperatures for extended periods of time (~15 hrs.) before measurements were obtained, however [1]. These data indicated emissivities of 0.04 - 0.06 in the 8 - 14 μm range for temperatures from 599 - 805 K. Measurements for our thimble material indicate an emissivity of 0.08 for this wavelength and temperature range. Therefore, selecting 0.045 as a reasonable value to represent polished aluminum in the 8 - 14 μm range, total normal emissivities for the thimble are expected to be about 78% higher than total normal emissivities of polished aluminum. Measurements for our cooling tube indicate an emissivity of 0.06 in the 8 - 14 μm range for the highest temperatures measured. Therefore, total normal emissivities for the cooling tube are expected to be about 20% higher than total normal emissivities of polished aluminum. Total hemispherical emissivities of polished aluminum samples range from approximately 0.04 to 0.06 over the temperature range 300 - 600 K [4].

3.2 Relation to hemispherical emissivities

Results discussed above refer to normal emissivities. In general, emissivity is independent of direction only for diffuse emitters. Since the emissivity of metals generally increases with angle away from the normal, the ratio of hemispherical to normal emissivity, ϵ/ϵ_n , for metals is generally greater than 1.0. In particular, this ratio varies from about 1.3 for low emissivities to about 0.9 at high emissivities as shown in Fig. 7 (reproduced from [2]). The ratio plotted in Fig. 7 is not exact, since it is based on inexact theory and the assumption that the index of refraction, n , is equal to the extinction coefficient, κ . In addition, these values correspond to the case of a polished surface. Unpolished surfaces would tend to have ϵ/ϵ_n values closer to 1.0. For the emissivity range of the samples included in this study, approximate values of ϵ/ϵ_n are tabulated in

Table 2. Ratio of hemispherical to normal emissivity for metallic surfaces.

	ϵ/ϵ_n
$\epsilon = 0$	1.33
0.05	1.27
0.10	1.225
0.15	1.185
0.20	1.145
0.25	1.105
0.30	1.075
0.35	1.055

Table 2 as a function of hemispherical emissivity [5]. For example, for a hemispherical emissivity of 0.05, ϵ/ϵ_n is 1.27. For a hemispherical emissivity of 0.3, however, ϵ/ϵ_n is only 1.075.

Another method for estimating the ϵ/ϵ_n ratio is provided in [2]. This method makes use of the following equations:

$$\epsilon/\epsilon_n = \frac{0.751\sqrt{r_e T} - 0.396r_e T}{0.576\sqrt{r_e T} - 0.124r_e T} \quad (0 < r_e T < 0.2) \quad (8)$$

$$\epsilon/\epsilon_n = \frac{0.698\sqrt{r_e T} - 0.266r_e T}{0.576\sqrt{r_e T} - 0.124r_e T} \quad (0.2 < r_e T < 0.5) \quad (9)$$

where r_e is the electrical resistivity of the surface material in ohm-cm. Using values of 72 and 4 $\mu\Omega$ -cm for the respective electrical resistivities of stainless steel (304) and aluminum alloy [8] at approximately 300 K, values of ϵ/ϵ_n equal to 1.24 and 1.29 are obtained. These values would be representative for polished stainless steel and aluminum samples at room temperature. Samples with roughness and/or oxidation will have values of ϵ/ϵ_n closer to 1.0. Also, the ratio of ϵ/ϵ_n is dependent on temperature. Fig. 7 is more useful for estimating ϵ/ϵ_n ratios at various temperatures when ϵ_n is known. Information on the temperature dependence of the relevant electrical resistivities would be needed in order to apply eqns. (8) and (9) at various temperatures.

3.3 Estimates of total, hemispherical emissivities

Estimates of total, hemispherical emissivities were obtained at 400 K and 800 K in the following

manner. Total normal emissivities were first estimated from the measured 8 - 14 μm values by comparing the measured values to the spectral normal data presented in Figs. 4 and 6. For example, for the safety rod, measurements agreed reasonably well with spectral normal data in the 8 - 14 μm range presented in Fig. 4 for the unoxidized sample. This spectral distribution was therefore assumed to be representative of the safety rod. To obtain a total normal emissivity at 400 K, the spectral value at 7.2 μm from Fig. 4 was assumed to be representative. For the 800 K total normal emissivity, the spectral value at 3.6 μm was assumed to be representative.

This procedure includes two additional assumptions. The first is that the spectral emissivity at the peak wavelength for emission is approximately equal to the total normal emissivity. This assumption is reasonable since the off-peak contributions fall off rapidly with wavelength. For example, at 800 K, the peak wavelength is approximately 3.6 μm and the blackbody distribution is down by almost an order of magnitude at 2 μm and 10 μm . The variation in spectral emissivities is small over this range and the average emissivity over this range is very close to the 4 μm value. The second assumption is that over the temperature range of 400 - 800 K, the spectral distributions of emissivity do not change significantly. This assumption will be reasonable as long as the surface condition is not significantly altered due to heating (eg. oxide layer formation). Furthermore, the measurements obtained in this series indicated very small changes in band spectral (8 - 14 μm) emissivities over the 400 - 800 K temperature range. Total hemispherical emissivities were estimated from the total normal values using ϵ/ϵ_n ratios from Fig. 7.

Estimated uncertainties for the total hemispherical emissivity estimates were obtained from an rms sum of the original measurement uncertainty for the 8 - 14 μm value, the uncertainty associated with the estimation of the total normal emissivity, and the uncertainty associated with the estimation of the total hemispherical emissivity. Therefore,

$$\delta\epsilon = \sqrt{(\delta\epsilon)_{\text{meas}}^2 + (\delta\epsilon)_{\lambda \rightarrow n}^2 + (\delta\epsilon)_{n \rightarrow h}^2} \quad (10)$$

The estimated uncertainty for the total normal emissivity was assumed to be 5% at 400 K and 15% at 800 K. The estimated uncertainty for the total hemispherical emissivity was assumed to be 15% of the normal-to-hemispherical correction plus 5% of the normal emissivity.

Best estimates of total hemispherical emissivities at 400, 550, 700, and 800 K are presented in Fig. 8, along with their estimated uncertainties. These values are also listed in Table 3.

Table 3. Estimates of total hemispherical emissivities and uncertainties for each sample.

	ϵ , safety rod	$\delta\epsilon$, safety rod	ϵ , thimble	$\delta\epsilon$, thimble	ϵ , cooling tube	$\delta\epsilon$, cooling tube
400 K	0.177	0.022	0.124	0.020	0.091	0.0194
550 K	0.209	0.021	0.128	0.0135	0.095	0.0115
700 K	0.236	0.029	0.143	0.018		
800 K	0.245	0.033	0.157	0.0225		

4. SUMMARY

Emissivity measurements have been obtained for selected materials used in a gamma-heating natural convection experiment. Three cylindrical samples were studied, including a 0.94 in. OD stainless steel rod, an aluminum tube (thimble) and an aluminum cooling tube, using an infrared pyrometer sensitive to the 8 - 14 μm wavelength range. Results have been compared to literature values and a methodology for estimation of total hemispherical emissivity for these samples has been applied.

5. References

1. Touloukian, Y. S., and DeWitt, D. P., eds., *Thermophysical Properties of Matter*, IFI/Plenum, TRPC Data Services. Vol. 7, 1970.
2. Siegel, R., and Howell, J. R., *Thermal Radiation Heat Transfer*, McGraw-Hill, 1972.
3. Sparrow, E. M., and Cess, R. D., *Radiation Heat Transfer*, augmented edition, McGraw-Hill, 1978.
4. Incropera, F. P., and DeWitt, D. P., *Fundamentals of Heat and Mass Transfer*, third ed., Wiley, 1990.
5. Dewitt, D. P., and Nutter, G. D., eds., *Theory and Practice of Radiation Thermometry*, Wiley, 1988.
6. Moffat, R. J., "Contributions to the Theory of Single-Sample Uncertainty Analysis," *Journal of Fluids Eng.*, Vol. 104, pp. 250-260, 1982.
7. Wolfram, S., *Mathematica, A System for Doing Mathematics by Computer*, Addison-Wesley, 1988.

Figure 1. Schematic of emissivity measurement set-up.

Figure 2. Comparison of predicted pyrometer response temperatures to indicated pyrometer temperatures for various emissivity settings.

Figure 3. Normal emissivities of stainless steel tube.

Figure 4. Normal spectral emissivities of stainless steel (304) from reference [1].

Figure 5. Normal emissivities of aluminum samples.

Figure 6. Normal spectral emissivities for polished aluminum from reference [1].

Figure 7. Relationship between normal and hemispherical emissivities for metals, from [2].

Figure 8. Best estimates of total hemispherical emissivities for all samples.

Appendix A
Infrared Pyrometer Characteristics and Specifications

Infra-red pyrometer characteristics

- Cassegrain optics focus infra-red radiation on thermopile detector
- Minimum spot size is 0.25" at 24"
- Filters limit the wavelength sensitivity range to 8-14 μm
- Microprocessor provides corrections for ϵ and T_a variations based on user input

Models

The Omegascope series is available in several models (identified by a serial number label on each instrument). The various models may be used for temperature measurement in general maintenance, product and process temperature monitoring, statistical quality control, and research. Each model (except OS-2101 and Agricultural units) includes a telescopic sight that increases aiming precision for small targets.

Low Temperature	OS-2101	Basic model; uses open-style sights.
Low Temperature Scope	OS-2102 S	Allows general-purpose measurement of smaller targets, at medium distances.
High Resolution	OS-2103 S	High-resolution model for general-purpose measurement of smaller targets at greater distances.
Close Focus 1	OS-2104 S	Special-purpose high-resolution models offering the capability to measure .25" (6.4mm) and .50" (12.7mm) targets at 24" (0.6m) and 48" (1.2m), respectively.
Close Focus 2	OS-2105 S	
Long Range	OS-2106 S	High-resolution model focused at infinity for long-range measurement applications, and general-purpose.
High Temperature	OS-3000 AS	High-temperature model for measuring metals, cement, glass, ceramics, heat-treating, etc.
Glass	Special Order	Designed specifically to measure glass surfaces.
Agricultural	Special Order	Measures temperature with 0.1 degree resolution for agricultural and laboratory applications.
Sub-Zero	Special Order	Measures temperatures from minus 110°F (-80°C) to 250°F (120°C) for food processing, agricultural, and other applications.

All models (except glass, agricultural and sub-zero) include the Reflected Ambient Temperature Compensation feature.

Omegascope Infrared Pyrometer Specifications

General Operating

Accuracy	±1% of reading, ± digit	
Repeatability	±0.5% of reading, ±1 digit	
Emissivity	0.10 to 1.00 in 0.01 steps, digital setting and display	
Reflected Ambient Temperature Input Range	LT: -17 to 1648°C	HT: 400-3000°C
Display Resolution	1.0 degree (0.1 for Agricultural unit) in TMP, MAX, MIN, DIF display 0.1 degree in AVG display below 1000°F (500°C)	
Response Time	250 milliseconds	
Power	9 Vdc	

General Environment

Operating	32 to 120°F	0 to 50°C
Storage	-40 to 150°F	-40 to 60°C

Temperature Range

Model	Degrees F	Degrees C
Low Temperature	-20 to 2500	-30 to 1400
Low Temperature Scope	-20 to 2500	-30 to 1400
High Resolution	-20 to 2500	-30 to 1400
Close Focus I, II	-20 to 2500	-30 to 1400
Long Range	-20 to 2500	-30 to 1400
High Temperature	750 to 5400	400 to 3000
Glass	200 to 3000	100 to 1600
Agricultural	-20 to 212	-30 to 100
Sub-Zero	-110 to 250	-80 to 120

Optical

Model	Distance-to-Size-Ratio At Focal Point	Minimum Spot At Distance	Spectral Response (μ)
Low Temperature	60:1	0.5" (1.3 cm) @ 30" (76 M)	8-14
Low Temperature Scope	60:1	1.0" (2.5 cm) @ 60" (152 cm)	8-14
High Resolution	90:1	1.0" (2.5 cm) @ 90 (230 cm)	8-14
Close Focus I	96:1	.25" (0.64 cm) @ 24" (61 cm)	8-14
Close Focus 2	96:1	.50" (1.3 cm) @ 48" (122 cm)	8-14
Long Range	96:1	10.0" (25.4 cm) @ 100 ft. (30.5 M)	8-14
High Temperature	167:1	1.1" (2.8 cm) @ 180" (457 cm)	2.1-2.3
Glass	60:1	1.0" (2.5 cm) @ 60" (152 cm)	4.9-5.3
Agricultural	15:1	2.6" (6.6 cm) @ 40" (102 cm)	8-14
Sub-Zero	30:1	1.3" (3.3 cm) @ 40" (102 cm)	8-14

Appendix B

Mathematica Algorithms for Calculating Emissivities and Uncertainties

Algorithm for calculating emissivity uncertainties:

```

a=3.742 10^8
b=1.439 10^4
c=5.67 10^-8
fint[x_] := a/c/(x^5(Exp[b/x]-1))

ftb[y_] := NIntegrate[fint[x], {x, 8 y, 14 y}]

ems[t1_, t2_] := (q12ra - sigma t2^4 ftb[t2])/
(sigma (t1^4 ftb[t1] - t2^4 ftb[t2]))

ta=295
ts=375
em=0.06
For[i=1, i<5, i++, ts=ts+25;
q12ra=sigma(em ts^4 ftb[ts] + (1-em) ta^4 ftb[ta]);
tsper=.01 (ts-273) + ts+1;
q12per=sigma(em tsper^4 ftb[tsper] + (1-em) ta^4 ftb[ta]);
dedts=ems[ts+1, ta] - ems[ts, ta];
dedta=ems[ts, ta+1] - ems[ts, ta];
dedq=1.82 10^7/(sigma (ts^4 ftb[ts] - ta^4 ftb[ta]));
delts=Max[.0075 (ts-273), 2.2];
delta=3;
delq=(q12per-q12ra)/(1.82 10^7);
dele=((dedts delts)^2 + (dedta delta)^2 + (dedq delq)^2)^.5;
Print[ts, dele]]

```

Algorithm for calculating an unknown emissivity based on readings obtained at some temperature other than the actual surface temperature:

(top values for em, ts, and ta are the "gun" values. Bottom values are the "actual" values.)

```

em=.11
ts=(52+459.67)/1.8
ta=30+273
q12ra=sigma(em ts^4 ftb[ts] + (1-em) ta^4 ftb[ta])
ts=(152+459.67)/1.8
ta=22+273
ems[ts, ta]

```


uncert 2

algorithm for calculating apparent temp from pyrometer
readings at different emissivity settings:

```
em=1.0  
ts=258+273  
ta=23+273  
q12ra=sigma(em ts^4 ftb[ts]+(1-em) ta^4 ftb[ta])  
em=1.0  
ts=531  
c2=(1-em)sigma ta^4 ftb[ta]  
c3=(q12ra-c2)/(em sigma ftb[ts])  
tapp=c3^0.25
```

END

**DATE
FILMED**

6/10/92