DOE/ER/13484-2

EFFECTS OF CRACK GEOMETRY AND MATERIAL BEHAVIOR ON

SCATTERING BY CRACKS

FOR QNDE APPLICATIONS

DE FG02-86ER13484

DOE/ER/13484--2

DE92 010856

Technical Progress Report

March 1, 1988 - August 30, 1989

prepared by

J. D. Achenbach

Center for Quality Engineering and Failure Prevention
Northwestern University
Evanston, IL 60208-3020

Telephone (709) 491-5527

September 15, 1989

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

db
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TABLE OF CONTENTS

	Page
1. Summary Description of Project - - - - -	1
2. Summary of Recent Results- - - - -	2
2.A Scattering by Macrocrack-Microcrack Configurations- -	4
2.B Reflection and Transmission by an Infinite Array of Randomly Oriented Cracks- - - - -	6
2.C Wave Propagation in a Cracked Solid- - - - -	7
3. Work in Progress- - - - -	8
3.A Modeling of the Crack Environment- - - - -	8
3.B Crack-Face Interactions- - - - -	10
3.C Reflection by Porosity in an Interface- - - - -	11
4. Personnel- - - - -	13
5. Oral Presentations on Work on this Project by P.I. since Sept. 1, 1986- - - - -	13
6. Publications since Sept. 1, 1986 - - - -	14

1. Summary Description of Project

Flaws in solid bodies can, in principle, be detected and characterized by their effect on an incident pulse of ultrasonic wave motion. In actual testing situations there are, of course, several complicating factors which may make it difficult to produce a signal that provides enough information to completely characterize the flaw.

Analytical and numerical results for ultrasonic wave scattering by a crack provide valuable quantitative information for methods to detect and characterize cracks. From the mathematical point of view an open crack is a surface which does not transmit tractions. The implementation of this statement in a mathematical formulation generally involves a number of idealizations. Thus, the faces of a perfect mathematical crack are taken as smooth. It is also assumed that they are infinitesimally close, even though it is supposed that the faces do not interact with each other.

Real cracks, particularly fatigue and stress corrosion cracks have rough faces, which may contact each other. Sometimes there is not a single crack, but rather a configuration of a principal crack and an adjoining satellite crack, for example, a macrocrack and a neighboring microcrack. It also frequently happens that other smaller scatterers are located near a crack. The secondary scattering from these inhomogeneities will also affect the overall scattered field. In work on this project we have investigated to what extent these complicating features of real cracks or systems of cracks can be accounted for in an analysis.

Geometrical irregularities and material inhomogeneities in the vicinity of a crack can significantly affect the scattered fields that are generated by incident ultrasonic waves. In work on this project we have obtained results that display the effect of deviations from a mathematically perfect

simple crack geometry. Most of the results have been obtained by formulating a set of singular integral equations for the fields on the boundaries of the scattering obstacles. These equations have been solved numerically by the boundary element method, and the scattered fields have subsequently been obtained by using representation integrals.

There are few exact closed-form analytical solutions to elastodynamic scattering problems. In a rigorous approach, often the best that can be done is to reduce the mathematical formulation to a form which is suitable for numerical work. Closed-form solutions can be obtained at high frequencies (Kirchhoff approximation or geometrical diffraction theory) or at low frequencies (Rayleigh approximation). However these approximations are of limited value for scattering in the mid-frequency range in which characteristic wavelengths of an incident displacement pulse are of the same order of magnitude as a characteristic length of the flaw. In that range it is necessary to use numerical methods; for example, numerical schemes to solve systems of governing integral equations, finite difference techniques, finite element techniques, T-matrix methods, etc.

2. Summary of Recent Results

In work carried out on this project, the usual mathematical modeling of ultrasonic wave scattering by flaws is being extended to account for several typical characteristics of fatigue and stress-corrosion cracks, and the environment of such cracks. Work has been completed on scattering by macrocrack-microcrack configurations. We have also investigated reflection and transmission by a flaw plane consisting of an infinite array of randomly oriented cracks. In another investigation the propagation of mechanical disturbances in solids with periodically distributed cracks has been studied.

Fig. 1 Crack configurations

2.A Scattering by Macrocrack-Microcrack Configurations

The perfect mathematical crack model is acceptable for a real crack, provided that the latter's faces are slightly separated and that the length characterizing crack-face roughness is much smaller than the dominant wavelength of an incident pulse of ultrasonic wave motion. When the faces of a crack are in contact and the crack is actually partially closed, or when there are two neighboring cracks, the model must be adjusted. In work recently completed we have assumed that a partially closed crack can be represented by a configuration of two neighboring cracks. The four configurations depicted in Fig. 1 have been considered.

The mathematical formulation used in this work is two-dimensional, and for a state of plane strain. The usual displacement boundary integral equation formulation for scattering by volume scatterers, disintegrates when the scatterer is reduced to a crack. Hence a traction boundary integral equation is used in this paper. The mathematical formulation for a single crack is well known. Here it has been extended to a two-crack configuration, the result being a system of four coupled singular integral equations for the general case. These boundary integral equations are highly singular, and they cannot be solved directly by numerical methods. To circumvent this difficulty a special approach has been developed by which the higher order singularity has been reduced to an integrable singularity. Numerical results for scattered fields and for elastodynamic stress-intensity factors for several configurations have been obtained by the boundary element method. The scattered field results apply to a partially closed crack as well as to two separate but neighboring cracks. The stress-intensity factors are intended to apply only to the case of separate cracks.

Fig. 2. Cracks with randomly distributed angles of orientation.

Publication

2.1 Ch. Zhang and J. D. Achenbach, "Scattering by Multiple Crack Configurations," J. Appl. Mech., to appear.

2.B Reflection and Transmission by an Infinite Array of Randomly Oriented Cracks

In this work the problem of scattering of an anti-plane shear wave by an infinite array of equally spaced but randomly oriented cracks in an isotropic elastic medium has been considered. The configuration is shown in Fig. 2. The work was motivated by interest in the detection and characterization of a flaw plane, i.e., a plane of microcracks, for purposes of the non-destructive evaluation of materials. To our knowledge, the problem that has been formulated is new, and a new technique has been developed to obtain the desired information. The analysis is within the context of a scalar formulation, but it is, in principle, straightforward to extend it to a vector formulation as for in-plane elasticity.

The problem has been formulated for an averaged scattered field, and a "periodization" technique has been developed to derive the governing singular integral equation for the conditionally averaged crack-opening displacement. The singular integral equation has been solved by splitting the kernel into a singular and a regular part. A point scatterer approximation was introduced for the part containing the regular kernel. The approximation has been checked by comparison with exact results for a deterministic periodic system. By using this approximation, the coherent part of the averaged reflection and transmission coefficients of zeroth order have been calculated for normal incidence, a completely random crack orientation, and various values of the wave number and the ratio of crack length and crack-center spacing. The problem was formulated in the context

of anti-plane shear waves. The results are, however, also applicable to reflection and transmission of acoustic or electromagnetic waves by an array of screens.

The main results of this work are (1) the derivation of the singular integral equation for the conditionally averaged crack-opening displacement, (2) the development of an approximate method for solving the singular integral equation, and (3) the evaluation of the coherent part of the averaged reflection and transmission coefficients.

It should be emphasized that our formulation is valid for an arbitrary probability density of the crack angle, and is not restricted to a uniformly random distribution. Even though we have concentrated on the random orientation of the scatterers, the technique we have developed applies equally well to a uniformly random location of the scatterers.

Publication

2.2 Y. Mikata and J.D. Achenbach, "Reflection and Transmission by an Infinite Array of Randomly Oriented Cracks," J. Acoust. Soc. Am. to appear.

2.C Wave Propagation in a Cracked Solid

The propagation of harmonic waves in a solid which contains distributed cracks is generally characterized by a dependence of the phase velocity on the frequency. This dependence may be difficult to analyze for other than long wavelengths and widely spaced cracks. In this work, it has been shown, however, that it is relatively simple to obtain a relation between phase velocity and frequency (a dispersion relation) over a range of wavelengths for a rather special distribution of cracks, namely one that displays double periodicity.

The cracks are parallel to the x-axis, and their centers are located at positions $x = 2ml$, $y = 2nh$ ($m, n = 0, \pm 1, \pm 2, \dots$). For waves propagating in the y-direction, a dispersion equation has been obtained. The derivation is based on the assumptions that the frequency is below a certain cut-off frequency and that the cracked planes, $y = 2nh$, are sufficiently distant from each other. These assumptions allow one to view the cracked planes as planes of homogeneous reflection and transmission. The reflection and transmission coefficients corresponding to a planar array of cracks have been used to obtain numerical results. Dispersion curves have been plotted for three values of the spacing between the cracked planes. An important feature of the results is the presence of passing and stopping bands. A simple method to calculate the slopes of the dispersion curves at the origin has also been developed.

Publication

- 2.3 Y. C. Angel and J. D. Achenbach, "Harmonic Waves in an Elastic Solid Containing a Doubly Periodic Array of Cracks," WAVE MOTION 9, 377-385, 1987.

3. Work in Progress

In this Section we briefly review work that is currently in progress.

3.A Modeling of the Crack Environment

It is usually assumed that the mechanical behavior in the environment of a crack does not differ from that of the gross material. This assumption is not always applicable. In this part of the work we are considering deviations due to local inhomogeneity and crack-tip plasticity.

Local inhomogeneity, particularly near the crack tip may be caused by the presence of microflaws. If the characteristic cross-sectional dimension of a flaw is l , we generally have $l/\lambda_L \ll 1$, where λ_L is the wavelength.

The presence of the region with flaws then effectively corresponds to an elastic inclusion in which the crack tip is embedded. If the characteristic dimension of the region with flaws is r_v , then the effect will be small for $r_v/\Lambda_L \ll 1$. For $r_v = \Lambda_L$ it may, however, be necessary to include a correction.

The immediate vicinity of a crack tip in a metal may also have been subjected to plastic deformation. This deformation may be characterized as small scale or large scale, when the characteristic dimension of the zone of plastic deformation, r_p , is small or of the same order of magnitude, respectively, as the dimension of the crack. The presence of a zone of plastic deformation may affect the scattered field so as to disguise the crack tip. It is conceivable that the plastic zone may distort the scattered field to the extent that the presence of an inclusion rather than a crack tip is suggested.

In the work in progress we are assuming that with regard to the incident ultrasonic pulse, a near-tip zone of plastic deformation as well as a zone of local inhomogeneity due to voids act as elastic inclusions with elastic constants that are different from those in the surrounding elastic material. Hence we are effectively considering scattering by a crack which itself is located in an inclusion. In a first approach we are assuming that the material properties of the near-tip region are only slightly different from those of the bulk material. This suggests the use of the Born approximation, whereby the field in the inclusion is taken to be the one generated by the incident field and the crack tip in a homogeneous material. This approximate approach has allowed us to compute the modified crack-tip

diffraction, and to make some parametrical studies on the influence of near-tip inhomogeneity.

3.B Crack-Face Interactions

A perfect mathematical crack is an infinitesimally thin crack with smooth faces. The effects of crack-face interaction are ignored in considerations based on the perfect mathematical crack. The failure processes that result in a crack generally produce rough crack faces. Once a crack has been opened and the crack faces have undergone some relative sliding displacement, it must be expected that the crack will never completely close again due to incompatibility of the rough crack faces. Under subsequent loading conditions the faces of the crack generally may not be free of surface tractions, as is assumed for a perfect mathematical crack.

It can be stated that the perfect-mathematical-crack results are valid for a real crack if the ratio of the crack-opening to the amplitude of the incident wave is larger than unity, and if the wavelength is much larger than a characteristic spacing length of the crack-face roughness.

The work completed on this project on both nonlinear and linear crack face interactions as well as the work on reflection and transmission by an array of microcracks, is applicable to specular reflections. In current work we are considering the corresponding effects on crack tip diffractions. These diffractions play an essential role in the crack-sizing method that has so far proven to be the most successful one. We are therefore, investigating the effect of near-tip constraints on the crack-tip diffraction. The near-tip constants are represented by a distribution of springs. These springs represent such effects as crack-face interactions, as discussed in earlier work on this project, but also residual cohesive

tractions if the fracture process has not been completed. It is to be expected that the strength of the tip-diffracted field can be significantly affected by the near-tip constraints. The effect can be investigated quantitatively by solving a canonical problem for the constraint-affected diffraction coefficients. In the first approach we are taking into account a distribution of springs of strength $\kappa(x)$ for normal interactions only. The constraining springs are applied over a length a only. The incident wave is a plane longitudinal or transverse wave. The two-dimensional diffraction problem can be solved by the use of Fourier transform methods and the Wiener-Hopf technique, while the diffraction coefficients can subsequently be obtained by application of the method of steepest descent to the integral representations for the diffracted field. Parametrical studies of the diffraction coefficients, which will contain $\kappa(x)$ and a , will reveal the effect of crack-tip constraints on the tip diffraction, at least in the far field.

The appropriate values for the crack-face constraints will be taken on the basis of the previous work. Thus, for essentially periodic constraints, equivalent to a distribution of microcracks with regular spacing we will take the constants obtained earlier, perhaps adjusted to decrease towards the crack tip.

3.C Reflection by Porosity in an Interface

Interfaces between materials of different mechanical properties occur more and more frequently in structural components for high-technology applications. Materials may be joined in various ways: by direct deposition of one on the other, by adhesion or by diffusion bonding. It has been well established that the integrity of the interface is usually the critical consideration for the overall quality of the component. Hence it

is extremely important to develop appropriate non-destructive methods of quantitative interface evaluation.

An interface can be substantially weakened by the presence of voids, such as a fairly uniform distribution of voids (porosity), or perhaps clusters of voids. In work in progress on this project we are investigating reflection and transmission by single spherical cavities, and periodic distributions of spherical cavities, which are located in the otherwise perfect interface of two elastic solids of different mechanical properties.

The scattering problem has been formulated rigorously, by taking advantage of the geometrical periodicity. Both the reflected and the transmitted wave motions have been expressed as superpositions of an infinite number of wave modes, each with its own cut-off frequency. At the cut-off frequency a mode converts from a standing into a propagating wavemode. The standing modes decay exponentially with distance to the plane of the centers of the cavities. At small frequencies only the lowest order modes of longitudinal and transverse wave motion are propagating. As the frequency increases more and more of the scattered waves convert from standing into propagating modes.

Reflection and transmission coefficients have been defined in terms of the coefficients of the zeroth order scattered waves. These coefficients have been computed by a novel application of the Betti-Rayleigh reciprocal theorem. They are expressed as integrals over the surface of a single cavity, in terms of the displacement components on the cavity surface. The system of singular integral equations for the displacement components has been solved numerically by the use of the boundary integral equation method.

4. Personnel

Principal Investigator: J. D. Achenbach

The following past and present Post-Doctoral Associates participated in work on this research project for various periods of time:

Y. C. Angel (now at Rice University)
M. Kitahara (now at Tokai University, Shizuoka, Japan)
Y. Mikata (now at U. of California, UCSD)
C. L. Scandrett (now at Naval Postgraduate School,
Monterey, CA)
D. A. Sotiropoulos
Ch. Zhang

Graduate Students:

G. Kechter
Y. -L. Xu

5. Oral Presentations on Work on this Project by P.I.
since Sept. 1, 1986

Invited lectures

1. Conference on Mathematical Modelling in Non-Destructive Testing, September 2 and 3, 1986, "Recent Developments in Ultrasonic Modelling in the USA", Cambridge, UK.
2. 1987 August J. Durelli Lecture, April 8, 1987, "Analytical Modeling of Ultrasonic Wave Scattering for QNDE Applications", The Catholic University of America.
3. Fifth Symposium on Energy Engineering Sciences, June 17-19, 1987, "Masking Effects of Microcracks, Voids and Near-Tip Mechanical Behavior on Crack Detection and Characterization", Argonne National Laboratory.
4. 1987 TMS Fall Meeting, October 11-15, 1987, "Effect of Near-Tip Inhomogeneities on Scattering of Ultrasonic Waves by Cracks," Symposium on Nondestructive Evaluation - Predictive and Descriptive Probes of Mechanical Behavior of Metals," Cincinnati, Ohio.

Invited Seminars

1. Rutgers University, Dept. of Mechanics and Materials Science, Oct. 30, 1986, "An Inverse QNDE Method for Crack Characterization".

conjunction with the integral representation for the scattered-field, see Refs.[3.5]-[3.6] of this Section.

In work carried out on this project, the usual mathematical modeling of ultrasonic wave scattering by flaws has been extended to account for several typical characteristics of fatigue and stress-corrosion cracks, and the environment of such cracks. Work has been completed on scattering by macrocrack-microcrack configurations, see Refs.[3.7]-[3.10]. References [3.11]-[3.12] are concerned with the effect of near-tip zones of different material properties on the scattered field.

We have also investigated reflection and transmission by a flaw plane consisting of infinite arrays of periodic and randomly oriented cracks [3.13]-[3.16]. In other investigations scattering by an inclusion with compliant interphase characteristics, [3.17], and the propagation of mechanical disturbances in solids with distributed cavities and cracks has been studied, [3.18]-[3.21].

6. Publications since September 1, 1986

- 3.1 (with C. L. Scandrett and G. A. Kriegsmann), "Scattering of a Pulse by a Cavity in an Elastic Half-Space," J. of Comp. Physics, 65, pp. 410-431, 1986.
- 3.2 (with C. L. Scandrett), "Time-Domain Finite Difference Calculations for Interaction of an Ultrasonic Wave with a Surface-Breaking Crack," WAVE MOTION, Vol. 9, pp. 171-190, 1987.
- 3.3 (with S. Hirose), WAVE MOTION, 10, pp. 59-72, 1988.
- 3.4 (with S. Hirose), "Time-Domain Boundary Element Analysis of Elastic Wave Interaction with a Crack," Int. J. for Numerical Methods in Engineering, in press.

- 3.5 (with D. A. Sotiropoulos and H. Zhu), "An Inverse Scattering Method to Characterize Inhomogeneities in Elastic Solids," J. Appl. Physics, 62(7), pp. 2771-2777, 1987.
- 3.6 (with D. A. Sotiropoulos and H. Zhu), "On the Direct and Inverse Elastic Wave Scattering Problem to Characterize Damage in Materials," in Review of Progress in Quantitative Nondestructive Evaluation, Vol. 6A, (edited by Donald O. Thompson and Dale E. Chimenti), Plenum Press, pp. 39-43, 1987.
- 3.7 (with Ch. Zhang), "Scattering by Multiple Crack Configurations," J. Appl. Mech., 55, pp. 104-110, 1988.
- 3.8 "Masking Effects of Microcracks, Voids and Near-Tip Mechanical Behavior on Crack Detection and Characterization," Proceedings of the Fifth Symposium on Energy Engineering Sciences, Instrumentation, Diagnostics, and Material Behavior, co-sponsored by U.S. Dept. of Energy and Argonne National Laboratory, pp. 153-160, 1987.
- 3.9 (with Ch. Zhang), "Effect of an Adjacent Cavity on the Interaction of Elastic Waves with a Crack," Int. J. of Engineering Science, in press.
- 3.10 J. Qu: "Elastic Wave Scattering by Macro-Micro Crack Configurations," Review of Progress in Quantitative NDE, Vol. 8, in press.
- 3.11 (with D. A. Sotiropoulos and Ch. Zhang), "Effects of Near-Tip Inhomogeneities on Scattering of Ultrasonic Waves by Cracks," Metallurgical Transactions, in press.
- 3.12 "Strength Evaluation by Ultrasonic Methods," Proc. Seventh International Conference on Fracture, Pergamon Press, in press.
- 3.13 (with Y. Mikata), "Reflection and Transmission by an Infinite Array of Randomly Oriented Cracks," J. Acoust. Soc. Am. Vol. 83, pp. 38-45. 1988.

- 3.14 (with Y. Mikata), "Interaction of Harmonic Waves with a Periodic Array of Inclined Cracks," Wave Motion, 10, 59-72, 1988.
- 3.15 (with M. Kitahara, Y. Mikata and D. A. Sotiropoulos), PAGEOPH, 128, pp. 101-118, 1988.
- 3.16 (with Y. Mikata), "Scattering by a Periodic Array of Collinear Cracks," Review of Progress in Quantitative NDE, Vol. 8, in press.
- 3.17 (with M. Kitahara and K. Nakagawa): "Backscatter from a Spherical Inclusion with Compliant Interphase Characteristics," Review of Progress in Quantitative NDE, Vol. 8, in press.
- 3.18 (with M. Kitahara), "Harmonic Waves in a Solid with a Periodic Distribution of Spherical Cavities," J. Acoust. Soc. Am. 81(3), pp. 595- 598, 1987.
- 3.19 (with Y. C. Angel), "Harmonic Waves in an Elastic Solid Containing a Doubly Periodic Array of Cracks," WAVE MOTION 9, pp. 377-385, 1987.
- 3.20 (with M. Kitahara), "BIE Method to Analyze Wave Motion in Solids with Periodically Distributed Cavities," Computer Methods in Applied Mechanics and Engineering, 64, pp. 523-536, 1987.
- 3.21 Y. Mikata, "Dispersion and Attenuation in a Randomly Cracked Medium," submitted for publication.

**DATE
FILMED**

5/04/92