WSRC-RD--91-16

DE92 009947

RECEIVED BY OST
MAR 19 1992

GAMMA-RAY SPECTROMETRY OF LDEF SAMPLES (U)

by

W. G. Winn

Westinghouse Savannah River Company
Savannah River Laboratory
Aiken, South Carolina 29808

DISCLAIMER

This is a DP Report

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This paper was prepared in connection with work done under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U.S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

4b

GAMMA-RAY SPECTROMETRY OF LDEF SAMPLES

(U)

Willard G. Winn

Westinghouse Savannah River Company
Savannah River Site
Aiken, SC 29808

SUMMARY

In January 1990, NASA retrieved the Long Duration Exposure Facility (LDEF), which had orbited the Earth since April 1984. The satellite had become slightly radioactive due to cosmic exposure, and NASA sought out low-level radiometric laboratories to provide ultra-sensitive analyses of samples from LDEF. The SRL Environmental Technology Radiometrics Group was selected by NASA as such a laboratory, and it received and analyzed LDEF samples during 1990 and early 1991.

A total of 31 samples from LDEF, including materials of aluminum, vanadium, and steel trunnions were analyzed by ultra-low-level gamma spectrometry. The study quantified particle induced activations of ^{22}Na , ^{46}Sc , ^{51}Cr , ^{54}Mn , ^{56}Co , ^{57}Co , ^{58}Co , and ^{60}Co . The samples of trunnion sections exhibited increasing activity toward the outer end of the trunnion and decreasing activity toward its radial center. The trunnion sections did not include end pieces, which have been reported to collect noticeable ^7Be on their leading surfaces. No significant ^7Be was detected in the samples analyzed.

The SRL Underground Counting Facility was used in this work. The facility is 50 ft underground, constructed with low-background shielding materials, and operated as a clean room. The most sensitive analyses were performed with a 90%-efficient HPGe gamma-ray detector, which is enclosed in a purged active/passive shield. Each sample was counted for 1-6 days in two orientations to yield more representative average activities for the sample. The non-standard geometries of the LDEF samples prompted the development of a novel calibration method, whereby the efficiency about the sample surfaces (measured with point sources) predicted the efficiency for the bulk sample.

The information contained in this article was developed during the course of work under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy.

TABLE OF CONTENTS

SUMMARY	i
I. INTRODUCTION	1
II. MEASUREMENTS	1
III. ANALYSES	2
HPGe Spectral Analyses	2
Calibrations	3
IV. RESULTS	5
V. DISCUSSION	6
Trunnions	6
Vanadium	8
Aluminum	9
ACKNOWLEDGEMENTS	9
REFERENCES	10
TABLES	11
1. Trunnion Disk Results	11
2. Trunnion Layer Results	12
3. Vanadium and Aluminum Sample Results	13
4. Cosmic Ray Interactions	14

TABLE OF CONTENTS (Continued)

FIGURES	15
1. LDEF Photographs	15
2. Background Spectrum	16
3. Active Shield Effects	17
4. Typical Spectrum Analyzed by GRABGAM	18
5. Efficiency Calibration	19
6. LDEF Sample Location Scheme	20
7. Trunnion Disk Sample Locations	21
8. Trunnion Axial Dependence	22
9. Trunnion Layer Locations	23
10. Trunnion Radial Dependence	24
11. Aluminum Sample Locations	25
12. Average Radial Profiles	26
 APPENDICIES	 +26
A. Background Spectrum Identifications	A-1
B. Detector Efficiency Calibrations	B-1
C. Sample Details	C-1

I. INTRODUCTION

The Long Duration Exposure Facility (LDEF) was placed in orbit about 250 miles above the Earth by the Challenger space shuttle in April of 1984. As implied by its name, the LDEF was geared to study long-term radiation effects in the near-Earth space¹. The results would be useful in the design of a future orbital space station. NASA had originally planned to retrieve the LDEF within a year; however, major obstacles, particularly those due to the Challenger disaster in 1986, delayed retrieval until January of 1990. Following this retrieval by the Columbia space shuttle, the LDEF was transported to Kennedy Space Center at Cape Canaveral, Florida. Photographs describing the sequence of these events are given in Figure 1.

Personnel at NASA Marshall Space Center initiated a program for radiometric analysis of the LDEF samples⁴. Due to extensive experience in ultra-low level counting of environmental samples at the SRL Underground Counting Facility, NASA selected it as one of the laboratories for LDEF analyses. SRL received its first LDEF samples on March 7, 1990, and a total of 68 gamma spectrometry analyses were conducted on 31 samples submitted during 1990-1991. Round-robin gamma analyses of these and/or similar samples were conducted at PNL, LNL, LBL, LLL, ORNL, TVA, and at NASA facilities in Houston, Texas and Huntsville, Alabama. To date, the SRS results have compared favorably with those reported at the other laboratories. ← ref. 1

This report emphasizes the measurements of the induced radioactivity in the LDEF samples submitted to SRS. These results will be used to appraise and improve models for characterizing trapped particles and cosmic rays²⁻⁴; however, this is beyond the scope of the present report. Yet, the report does identify particle reactions for producing the observed radionuclides, and examines trends within the data. A special emphasis is also given to the methods used to develop efficiencies for these somewhat unorthodox samples.

II. MEASUREMENTS

The SRL Underground Counting Facility⁵ was used to conduct gamma spectrometry on the LDEF samples. This facility is 50 ft below ground and constructed with low-background materials. Pre-WWII steel comprises the 4 in walls of the counting chamber, which is shielded by 4-7 ft of specular hemitite. The total

overburden is equivalent to 104 ft of water shielding, which reduces the cosmic background by an order of magnitude. The facility operates as a Class 10,000 clean room, whereby airborne particulates are removed by filtering. The very stable spectrometry electronics use an uninterruptable power supply to protect against data losses during extended counting times.

HPGe detectors with standard efficiencies of 20%, 25%, and 90% were used in this study. A low-level lead shield encloses each detector and its sample cavity, which is purged of radon with the nitrogen that evaporates from its LN₂ dewar. The 90% HPGe has an inner shield of cadmium and copper to reduce X-ray backgrounds induced in the shielding by gammas from the sample. Figure 2 gives a typical background spectrum for this detector, as applicable in most of the present study. The background peaks are discussed further in Appendix A. Near the end of the study, the detector background was further reduced with an active plastic-scintillator shield, which detects cosmic background events in anticoincidence with the gamma counting to veto this background. Figure 3 gives a schematic of the 90% HPGe and illustrates the performance of the active shield in reducing the cosmic continuum. In the present study, which used 1-6 day counting intervals, estimated detection limits⁶ for a ⁶⁰Co point source atop these detectors ranged from 0.04 to 0.4 pCi.

A total of 31 LDEF samples were examined by HPGe gamma spectrometry. The samples were trunnion disks and rectangular slabs of steel, vanadium, and aluminum. The disks had 3.25 in diameter and 0.4-0.9 in thickness; the slabs had maximum dimensions of 2x2 in² area and 0.35 in thickness. Some of the slab samples were from radial layers of the trunnion disks. Detailed sample descriptions are given in Appendix C. Each sample was counted with one side facing the detector and then recounted with its other side facing the detector, so that activity distributions within the sample could be detected and averaged.

Detector efficiency calibration for the above samples used a method of mapping the point source efficiency over the sample surfaces. Point sources of ⁵⁴Mn, ⁵⁷Co, ⁶⁰Co, ¹³³Ba, and ¹³⁷Cs were used. A paper mapping grid was developed for sample and source positioning. Such a non-destructive calibration technique was important in this work, because NASA required that the samples be returned intact for round-robin analyses at other laboratories.

III. ANALYSES

HPGe Spectral Analyses

The HPGe data were collected as 4000 channel gamma spectra, as illustrated in Figure 4. All spectra were in the form of ADCAM files, as developed by EG&G ORTEC. The GRABGAM code⁵, which was

developed at SRL for low-level counting, analyzed the spectra. This code uses three area trapping windows to identify prospective peaks. The narrowest window makes the first scan, so that any significant multiplet features can be identified. The middle window scans next. Finally, the largest window provides the best sensitivity for picking out peaks with low counting statistics. These candidate peaks are examined as integral probability functions $F(x)$ per channel x , to provide better statistics than afforded by fitting the peak to a differential probability $f(x)dx$; such enhanced statistics are useful in characterizing the centroids and widths of low-level peaks. Following the analysis, any peak contributions from the background spectrum, such as that of Figure 2, are subtracted.

GRABGAM also permits development of calibration curves for unusual geometries. Here $\log(\text{eff})$ vs $\log(E)$ efficiency curves may be fitted as a hyperbola, cubic polynomial with or without crossover, and a combination of these. Calibration analyses for the LDEF samples are discussed below.

Calibrations

Trunnion Disks. The counting geometry for a disk sample is given in Figure 5, along with the point sources locations used for calibration. Each point source spectrum yielded an efficiency $\epsilon(r,h)$, where r and h are the radial and height coordinates relative to the disk. The efficiency ϵ of a disk of uniform activity is the average of $\epsilon(r,h)$ over the disk, viz.

$$\epsilon = \frac{\int_V \epsilon(r,h) 2\pi r dr dh}{\int_V 2\pi r dr dh} \quad (1)$$

where V is the disk volume. The only measured $\epsilon(r,h)$ are the $\epsilon(r,h_t)$ and $\epsilon(r,h_b)$ on top and bottom surfaces of the disk; thus, a model is needed to infer the $\epsilon(r,h)$ within the disk. The model assumed in the present work was

$$\epsilon(r,h) = g(r) e^{-U(r)h} \quad (2)$$

where the h -dependence is exponential and the r -dependence is dictated by functions $g(r)$ and $U(r)$. An exponential is supported experimentally^{7,8}, and it models both geometry and material absorption dependences of the efficiency, as discussed in Appendix B.

Substituting Equation 2 into Equation 1 yields

$$\epsilon = \frac{\int_A \epsilon(r) 2\pi r dr}{\int_A 2\pi r dr} , \quad (3)$$

where $\epsilon(r)$, resulting from integrals over h , is given by

$$\epsilon(r) = g(r) \frac{e^{-U(r)h_t} - e^{-U(r)h_b}}{-U(r)[h_t - h_b]} = \frac{\epsilon(r, h_t) - \epsilon(r, h_b)}{\ln[\epsilon(r, h_t)/\epsilon(r, h_b)]} \quad (4)$$

Note that $\epsilon(r)$ is an exponential average along h within the sample volume, but it depends only values $\epsilon(r, h_t)$ and $\epsilon(r, h_b)$ measured on the surface outside the volume.

Individual $\epsilon(r)$ were determined using Equation 4 with experimental measurements, and these values were fitted to a function

$$\epsilon(r) = A - B r^p , \quad (5)$$

where A , B , and p are positive constants, and p is approximately equal to 2. Integrating this expression for $\epsilon(r)$ in Equation 3 yields

$$\epsilon = A - [2/(2+p)] B [r_d]^p , \quad (6)$$

where $r = r_d$ is the radius of the trunnion disk. Values of ϵ were determined as a function of energy, using the $\epsilon(r, h_t)$ and $\epsilon(r, h_b)$ point source measurements at different energies. The analysis details, given in Appendix B, indicate that the resulting ϵ are accurate within 5%.

Metal Slabs. Efficiencies for the rectangular metal slabs were determined using techniques similar to those for the trunnion disks. However, because the slabs were smaller in area and thickness, an effectively constant $U(r) = U$ was assumed, as consistent with experimental results^{7,8}, so that Equation 2 could be expressed with separable variables in r and h , viz.

$$\epsilon(r, h) = \epsilon(r, h_b) e^{-U(h-h_b)} \quad (7)$$

When inserted in Equation 1, this $\epsilon(r, h)$ yields

$$\epsilon = \frac{\int \epsilon(r, h_b) 2\pi r dr}{\int 2\pi r dr} \times \frac{1 - e^{-U(h_t-h_b)}}{U(h_t - h_b)} , \quad (8)$$

where the first term is numerically integrated over the rectangular bottom surface and the second term has already been integrated over h . The point source mappings on the detector surface are used to determine the first term. The second term requires a knowledge of U , which may be expressed as

$$U = c + \mu f \quad , \quad (9)$$

where c models the geometry dependence and μf models the material absorption. Here, the material attenuation coefficient μ is increased by a factor of f to correct for the average attenuation path, which is somewhat greater than h . The entire energy-dependence of U is contained in μ , as c and f are purely geometrical parameters. Thus, just two experimental measurements of U for different μ , which are known from tabulations⁹, yield a c and f that can predict U for any other μ . The present study determined c and f using μ corresponding to experimental measurements with 661 keV and 1332 keV gammas. Appendix B provides further details on the slab calibrations, including a relatively large summing correction that needed to be developed for ^{22}Na produced in the aluminum slabs.

IV. RESULTS

The respective results for trunnion disks, trunnion radial layers, vanadium slabs, and aluminum slabs are summarized in Tables 1, 2, and 3. Figure 6 gives the location of the samples on the LDEF. Additional details are given below and in Appendix C.

Trunnion disk sample results are summarized in Table 1 and correspond to data locations in Figure 7. Specific activities are given for ^7Be , ^{46}Sc , ^{51}Cr , ^{54}Mn , ^{56}Mn , ^{57}Co , ^{58}Co , and ^{60}Co , where ^{54}Mn is dominant and ^7Be is only marginally detected at best. Here the results from counting both sides of the disk have been averaged to yield the values presented. A $(1/\sigma^2)$ -weighted average was used, as the values with either side of the disk facing the detector generally agreed to within the counting errors. An exception was for sample LHB, where a 7.5% difference in ^{54}Mn was noted; but an even-weighted average for this case was the same as the $(1/\sigma^2)$ -weighted average because the errors were identical. Figure 8 plots the disk results for ^{54}Mn and ^{57}Co as a function of axial position along the trunnion, showing that these activities decrease as the position nears the LDEF end of the trunnion from the space end.

Trunnion radial layer activities are given in Table 2 and their sample locations are identified in Figure 9. The only significant radionuclides detected in these relatively small samples were ^{54}Mn and ^{57}Co . The results given are the average from counting both sides of the sample. An even-weighted average was

used as the activities for the two sides often differed significantly. Figure 10 plots the layer results, showing that the activities increase with increasing radial position of the trunnion. The data also suggest that the radial profiles on the space side of the trunnion differ from those on the Earth side.

Vanadium and aluminum sample activities are presented in Table 3. Detailed aluminum locations are given in Figure 11. Only ^{46}Sc was detected in the vanadium and only ^{22}Na was detected in the aluminum. Even-weighted averages of the results for each sample side are given, as these properly address differences between the two sides.

V. DISCUSSION

The LDEF samples examined in the present work implied cosmic activations induced by protons and neutrons, as summarized in Table 4. Also listed is the production of ^7Be ; however, little if any ^7Be was observed. Noticeable ^7Be had been reported on samples with leading surfaces that can collect particles in the LDEF path¹⁰, but none of the samples analyzed at SRS had such surfaces.

Trunnions

The trunnion samples were sufficient in number to provide trend data. Figures 7 and 9 show activity trends of ^{54}Mn and ^{57}Co along the axial (z) and radial (r) coordinates. The activities decrease as the z-position becomes closer to the LDEF body. The activities also decrease as the r-position decreases. Both decreasing trends are consistent with increased cosmic-ray shielding. In addition, the LH or westward-facing trunnion was activated somewhat more than the RH or eastward-facing trunnion, and this is a signature of the trapped proton anisotropy in the South Atlantic Anomaly region³. This anisotropy is caused by the Earth's magnetic field. The results are further supported by independent measurements on trunnions⁸, which are consistent for predictions for trapped and galactic protons⁴.

The data of Figures 8 and 10 also provide a self-consistency test between the modelled gamma efficiencies for the layer and disk samples. The two radial profiles (earth side and space side) for ^{54}Mn were combined to yield their average radial profile in Figure 12, where it is shown that the activity $A(r)$ is represented by

$$A(r) = B + C e^{Dr} \quad (10)$$

The average $A(r) = A_{av}$ over the trunnion range of $r = 0$ to r_d is then given as

$$A_{av} = \frac{\int A(r) 2\pi r dr}{\int 2\pi r dr} = B + 2C/Dr_d [e^{Dr_d} + (1-e^{Dr_d})/Dr_d] \quad (11)$$

Using the parameters for ^{54}Mn in Figure 11, $A_{av} = 79.8$ pCi/Kg for the RHG trunnion, which is consistent with the RH-trunnion trend in Figure 8; for comparison, the adjacent RHF trunnion disk value was 78.98 ± 1.34 pCi/Kg. Although the ^{57}Co radial profile is consistent with that of the ^{54}Mn , the imprecise data allow rather different profiles as well. However, no reasonable ^{57}Co profile yielded an A_{av} that agreed well with that for the corresponding trunnion disk. Specifically, the reasonable ^{57}Co profiles predicted A_{av} in the range of 10.5 - 13.7 pCi/Kg, while the adjacent RHF trunnion disk measurement was 7.00 ± 0.59 pCi/Kg.

The above comparison neglects the impact of the radial activity profile on the detection efficiency of the disk. Addressing this profile $p(r)$, which is directly proportional to $A(r)$, the corresponding efficiency ϵ_p is given as

$$\epsilon_p = \frac{\int_A p(r) \epsilon(r) 2\pi r dr}{\int_A p(r) 2\pi r dr} \quad (12)$$

The tabulated disk values should be corrected by a factor of ϵ/ϵ_p . Using the profile of Equation 10 for the RHG layers and the $\epsilon(r)$ measured for the adjacent RHF disk, an $\epsilon/\epsilon_p = 1.022$ was calculated for ^{54}Mn . Applying this correction to the ^{54}Mn of RHF disk yields 80.73 ± 1.37 pCi/Kg compared with the 79.8 pCi/Kg determined from layers of the adjacent RHG disk. A similar treatment using the same $p(r)$ with the ^{57}Co $\epsilon(r)$ also yields a small correction, which does not resolve the above difference between the ^{57}Co layer and disk results. Apparently, a different $p(r)$ applies for ^{57}Co . Using a $p(r) = kr^2$ profile, which corresponds to the lowest reasonable $A_{av} = 10.5$ pCi/Kg for RHG, the resulting $\epsilon/\epsilon_p = 1.269$ for RHF yields 8.88 ± 0.75 pCi/Kg. This illustrates that the ^{57}Co layer and disk results may become more consistent depending on the detailed nature of $p(r)$.

The trunnion disk results of Table 1 are all based on the assumption of uniform sample activities. Because appropriate ϵ/ϵ_p corrections are not generally available for these samples, such corrections were not applied. At the same time, a single available example for correcting ^{54}Mn illustrated a small correction in this case, implying that ^{54}Mn values in Table 1 are reasonably accurate. Values for other radio-isotopes of Table 1 can also be considered accurate if their corresponding $p(r)$ are

in reasonable agreement with that for ^{54}Mn . However, caution should be exercised here, as the ϵ/ϵ_p examination for ^{57}Co implied a quite different $p(r)$, suggesting that the ^{57}Co of Table 1 might need to be increased by a factor of 1.6 ± 0.3 . Finally, these observations suggest scrutiny in comparing round-robin results from the different participating laboratories, because the ϵ determined for the various detectors will need to be corrected by their different ϵ/ϵ_p before precise agreement can be expected. Unfortunately, current experimental data appear insufficient for determining these ϵ/ϵ_p ; however, model predictions based on particle fluxes may be possible^{3,4}.

Vanadium

The ^{46}Sc activated in vanadium indicated some trends; however, the photographs suggest that some of the samples may have been shielded so that only signatures of these trends are evident. The corresponding data of Table 3 are discussed below for signatures of anisotropic radiation received by the space/Earth ends and east/west sides of LDEF.

The ^{46}Sc density of two samples (I-H12-VA and I-H12-VB) on the space end of LDEF was about 30% larger than that of a single sample (G12-A2-FNV) on the Earth end; however, the error for the comparison is also about 30%. Because the photographs imply that the space end samples were probably more shielded, the observation implies that the radiation received from the space side is greater, which is consistent with the Earth acting as a cosmic shield for irradiation aimed at the Earth end of LDEF.

The ^{46}Sc density of a sample (I-F2-V) on the west side of LDEF is only about 5% larger than that of a sample (I-C9-V) on the east side, and the error for the comparison exceeds 5%. However, the photographs imply that the sample on the west side is more shielded, suggesting that the radiation from the west is higher than that from the east. Such anisotropy for trapped protons is well known and called the South Atlantic Anomaly⁴.

Aluminum

The ^{22}Na activated in aluminum supports the anisotropic trends more dramatically than the vanadium results. In logical order of development, the evidence for east/west and space/Earth anisotropies are discussed below, using data of Table 3 and the location information of Figures 6 and 11.

Two aluminum samples of the keel plate are on opposite sides of the keel and tend to be shielded from each other by the keel. Consequently, one sample (KP-3) received radiation preferentially from the west and the other (KP-10) from the east. The ^{22}Na

density of the west side sample was $48 \pm 6\%$ higher than that of the east side sample, showing an unmistakable signature for the east/west anisotropy.

The keel itself is midway between the space and Earth ends, so that the aluminum samples (KP-3 and KP-10) of the keel plate are closer to the space end than are the two samples (ESR-1 and ESR-2) of the retainer ring on the Earth end. The ^{22}Na densities of the two samples from the retainer ring essentially agree, having a difference of $1.2 \pm 4.2\%$, as these samples were both unshielded and exposed to the same radiation. Both keel plate samples were shielded, so that a hypothetical unshielded sample at this location would have ^{22}Na density in excess of either of the measured samples, but not more than their sum. Thus, the ^{22}Na density of the hypothetical unshielded keel plate sample would be 23-105% larger than that of the retainer ring samples, indicating strong evidence for the space/Earth anisotropy.

ACKNOWLEDGEMENTS

C.D. Ouzts is thanked for counting the LDEF samples and assisting with the development of the detector efficiency calibrations. Confirmation measurements supporting the efficiency model were provided by David Lindstrom, NASA Johnson Space Center, Houston, Texas. Guidance and partial funding for this project were provided through the efforts of G.J. Fishman and B.A. Harmon, NASA Marshall Space Center, Huntsville, Alabama. Also, information contained in this work was developed during the course of work under Contract No. DE-AC09-89SR18035 with the U.S. Department of Energy.

REFERENCES

1. G.J. Fishman, T.A. Parnell, and B.A. Harmon, "Long Duration Exposure Facility (LDEF) Induced Radioactivity Plan", NASA Marshall Space Center Report [Astrophysics Division, Space Science Laboratory] (December, 1989).
2. E.V. Benton and W. Heinrich, "Ionizing Radiation Exposure on LDEF", University of San Francisco Report USF-TR-77 (August, 1990).
3. T.W. Armstrong and B.L. Colborn, "Scoping Estimates of the LDEF Satellite Induced Radioactivity", Science Applications International Corp. Report SAIC-90/1462 (September 1990)
4. T.W. Armstrong and B.L. Colborn, "Radiation Calculations and Comparisons with Data", First LDEF Post-Retrieval Symposium, NASA Conference in Kissimmee, Florida (June 2-8, 1991) - to be published.
5. W.G. Winn, W.W. Bowman, and A.L. Boni, "Ultra-Clean Underground Counting Facility for Low-Level Environmental Samples", The Science of the Total Environment 69, 107 (1988). [Also available as USDOE SRL Report DP-1747, 57 pp (1987)].
6. W.G. Winn, "Ultrasensitive Examination of Environmental Samples by SRL Underground Counting Facility", Trans. Am. Nuc. Soc. 54, 34 (1987).
7. Dave Lindstrom, report letter on LDEF results, NASA Johnson Space Center, Houston, Texas (May 6, 1991).
8. C.E. Moss and R.C. Reedy, "Measurements of Induced Radioactivity in Some LDEF Samples", First LDEF Post-Retrieval Symposium, NASA Conference in Kissimmee, Florida (June 2-8, 1991) - to be published.
9. K. Debertin and R.G. Helmer, Gamma- and X-ray Spectrometry with Semiconductor Detectors, North-Holland, Elsevier Science Publishing Co., New York (1988).
10. G.J. Fishman, B.A. Harmon, et al, "Observation of ^7Be on the Surface of LDEF Spacecraft", Nature, 439, 678 (1991).
11. W.G. Winn and R.A. Sigg, "Pre-Operational Radio-Environmental Studies of Plant Vogtle", USDOE SRS Report WSRC-RP-89-161 (May 1, 1989).

Table 1. Trunnion Disk Results

Decay Correction Date - January 20, 1990

Sample	Isotopic Activities in pCi/Kg Sample							
	Be-7	Sc-46	Cr-51	Mn-54	Co-56	Co-57	Co-58	Co-60
LHB	-	4.31 ±.59	-	120.21 ±1.53	4.58 ±.73	15.17 ±.73	3.31 ±1.15	1.96 ±.18
LHE	-	4.57 ±.71	-	95.21 ±1.75	2.92 ±.77	9.60 ±.66	1.33 ±1.35	1.59 ±.30
LHF	-	3.37 ±.51	-	100.50 ±1.41	4.84 ±.75	10.47 ±.63	4.06 ±1.16	1.40 ±.19
LHP	0.95 ±3.29	3.53 ±.20	16.38 ±7.38	79.43 ±.68	2.65 ±.21	7.48 ±.28	4.90 ±.33	1.58 ±.11
LHR	-7.48 ±3.65	3.78 ±.21	34.35 ±8.43	76.71 ±.68	2.66 ±.23	7.23 ±.36	4.68 ±.35	1.52 ±.11
LHS	2.56 ±3.28	4.34 ±.19	23.14 ±8.15	75.25 ±.59	2.53 ±.20	6.22 ±.25	4.92 ±.30	1.55 ±.09
RHB	-	5.04 ±1.00	-	82.52 ±1.36	3.21 ±.79	7.34 ±.59	4.67 ±1.27	1.39 ±.25
RHE	-	1.96 ±.75	-	79.77 ±1.57	2.15 ±.95	6.63 ±.57	2.35 ±1.27	1.16 ±.22
RHF	-	2.99 ±.64	-	78.98 ±1.34	3.75 ±.89	7.00 ±.59	2.45 ±1.26	1.32 ±.20
RHP	5.36 ±3.53	3.46 ±.21	35.22 ±8.84	72.56 ±.66	2.67 ±.22	7.28 ±.30	4.39 ±.33	1.45 ±.11
RHR	8.75 ±3.07	3.48 ±.19	26.16 ±8.13	72.75 ±.60	2.41 ±.19	6.20 ±.24	4.29 ±.30	1.55 ±.09
RHS	2.67 ±3.74	3.94 ±.23	31.89 ±10.08	74.66 ±.71	2.73 ±.25	6.01 ±.32	4.32 ±.41	1.44 ±.12

All errors are 1- σ counting errors

Table 2. Trunnion Layer Results

Decay Correction Date: January 20, 1990

Space Side			Earth Side		
<u>RH-G-SP-</u>	<u>pCi/Kg Sample</u>		<u>RH-G-ER-</u>	<u>pCi/Kg Sample</u>	
	<u>Mn-54</u>	<u>Co-57</u>		<u>Mn-54</u>	<u>Co-57</u>
2	95.10 ±3.44	19.57 ±3.17	2	98.46 ±3.60	17.50 ±2.51
3	83.24 ±2.77	14.78 ±1.88	3	93.62 ±2.04	15.02 ±1.69
4	77.62 ±2.25	11.98 ±1.72	4	87.82 ±2.36	17.48 ±2.22
5	70.89 ±1.44	12.18 ±1.27	5	80.00 ±1.47	10.92 ±1.19
6	70.26 ±1.63	12.74 ±1.43	6	76.64 ±1.63	12.07 ±1.22

All errors are 1- σ counting errors

Table 3. Vanadium and Aluminum Sample Results

Decay Correction Date: January 20, 1990

Vanadium	
<u>Sample</u>	<u>pCi/Kg Sample</u> <u>Sc-46</u>
G12-A2-FNV	16.00 ±1.32
I-C9-V	20.24 ±1.51
I-F2-V	21.12 ±2.70
I-H12-VA	19.82 ±12.84
I-H12-VB	21.59 ±6.77

Aluminum	
<u>Sample</u>	<u>pCi/Kg Sample</u> <u>Na-22</u>
ESR-1	90.60 ±3.31
ESR-5	91.70 ±1.94
KP-3	111.47 ±1.95
KP-10	75.33 ±2.60

All errors are 1- σ counting errors

Table 4. Cosmic-Induced Radionuclides in LDEF Samples

RADIONUCLIDE PRODUCTION REACTIONS

Cosmic Particle		Target Nuclide		Radio-Nuclide		Residual Particles
<u>Aluminum</u>						
p	+	^{27}Al	----->	^{22}Na	+	spallation
<u>Vanadium</u>						
p	+	^{51}V	----->	^{46}Sc	+	spallation
<u>Iron/Nickel</u>						
p	+	^{54}Fe	----->	^{51}Cr	+	2α
n	+	^{56}Fe	----->	^{56}Co	+	p
n	+	^{58}Ni	----->	^{58}Co	+	α
p	+	^{56}Fe	----->	^{54}Mn	+	$2p + n$
p	+	^{58}Ni	----->	^{56}Co	+	$2p + n$
p	+	^{58}Ni	----->	^{57}Co	+	$2p$
n	+	^{58}Ni	----->	^{58}Co	+	p
n	+	^{59}Co	----->	^{60}Co

Figure 1. LDEF Historical Events

The LDEF events include the following: (a) Challenger places LDEF in Earth orbit, April 1984. (b) LDEF remains in orbit until retrieved by Columbia in January 1990. (c) Sample retrieval operations are underway at Kennedy Space Center, February 1990. (d) Initial samples analyzed at SRS Underground Counting Facility, March 1990.

Figure 2. Background Spectrum
Typical background of 90% HPGe During LDEF Analyses.

(a)

90% HPGE DETECTOR WITH ACTIVE/PASSIVE SHIELD AND NITROGEN PURGE

(See photograph on left.)

Figure 3. Detector Shielding

90% HPGe detector (a) shielding configuration and (b) effect of active shield in reducing continuum background.

Sample LHS

Figure 4. LDEF Sample Spectrum

Typical trunnion sample spectrum with 90% HPGe detector.

EFFICIENCY CALIBRATION

DATA

ANALYSIS

(1) Average exponentially over sample height

$$\epsilon(r) = \frac{\epsilon(r, h_t) - \epsilon(r, h_b)}{\ln [\epsilon(r, h_t) / \epsilon(r, h_b)]}$$

(2) Fit radial dependence

$$\epsilon(r) = A - B r^p$$

(3) Average over sample radial areas

$$\epsilon = A - [2/(2+p)] B [r_{\max}]^p$$

Figure 5. Overview of Efficiency Calibration Method

LDEF Induced Activity Analysis

Figure 6. LDEF Location Scheme

Location of Radionuclide Samples taken from LDEF, with radial locations 1-12 and axial locations A-F.

Figure 7. Location Scheme for LDEF Trunnion Samples

Trunnion Disk Samples

Figure 8. Activity of Trunnion Disk Samples

The trunnion activity axial dependence is given for the west (LH) and east (RH) trunnions on the Earth end of LDEF. The activity error bars are 1- σ counting errors, and position error bars are the widths of the layers.

Figure 9. Location Scheme for Trunnion Layer Samples

RH-G Trunnion Layer Samples

Figure 10. Activity of Trunnion Layer Samples

The RH-G trunnion activity radial dependence is given. The activity error bars are 1- σ counting errors, and position error bars are the widths of the layers.

(a) Keel Plate

(b) End Support Retainer Plate

//
Figure X. Detailed Locations of Aluminum Samples

Aluminum samples analyzed at SRS were (a) keel plate samples KP-3 and KP-10 and (b) end-support plate samples ESR-1 and ESR-5.

Figure 12. Trunnion Layer Averages

The trunnion radial profile points are averaged, and smooth curves are developed to predict the average activities A_{av} .

APPENDIX A. BACKGROUND SPECTRUM IDENTIFICATIONS

The table below describes peaks in the background spectrum in Figure 2. These backgrounds are representative of the bulk of the data collected with the 90% HPGe detector during this work. The active shield became of use later in the study, causing reduction in the continuum background and the 511.0 keV annihilation gamma, as illustrated in Figure 3.

Energy keV	Source	Intensity counts/hr
73	Pb K α 2 X-ray	1.0 $\pm$ 0.3
75	Pb K α 1 X-ray	2.5 $\pm$ 0.5
85	Pb K β 1 X-ray	5.3 $\pm$ 0.6
88	Pb K β 2 X-ray	1.6 $\pm$ 0.3
511.3	Annihilation	31.9 $\pm$ 0.7
558.6	Cd-114*	2.8 $\pm$ 0.3
570.0	Pb-207m*	1.2 $\pm$ 0.3
583.1	Tl-208	1.0 $\pm$ 0.3
651.3	Cd-114*	0.8 $\pm$ 0.3
803.1	Po-210	1.1 $\pm$ 0.2
1063.4	Pb-207m*	1.3 $\pm$ 0.2
1460.8	K-40	1.2 $\pm$ 0.4

* These isotopes are produced in equilibrium with neutrons from cosmic rays. Prompt reaction gammas for transitions in Cd-114 are produced by Cd-113(n, γ) and Cd-114(n,n'). Effectively prompt gammas from Pb-207m(0.8s) are produced by Pb-207(n,n') and Pb-208(n,2n).

APPENDIX B. DETECTOR EFFICIENCY CALIBRATIONS

General Theory

The basic model for the calibration is given in Equation 2 of the main text as

$$\epsilon(r, h) = g(r) e^{-U(r)h}, \quad (B-1)$$

where r and h are the coordinates within the sample. Although experimental support for this model has been cited^{7,8}, it is worthwhile to examine it mathematically.

The basis for the $e^{-U(r)h}$ dependence of $\epsilon(r, h)$ results from the fact that at any point in the sample, the efficiency can be expressed as the product of a k/R^2 geometry factor and a r -attenuation factor $e^{-\mu h \sec \theta}$, where k is a constant, R is the effective source-to-detector distance, μ is the r -attenuation coefficient for the sample, and $h \sec \theta$ is the portion of R within the sample. Referring to Figure B-1, $\theta = \sin^{-1}(r/R)$, so that $\sec \theta = f(r)$. Thus,

$$\epsilon(r, h) = k e^{-\mu h \sec \theta} / R^2 = k e^{-\mu h f(r)} e^{-2 \ln(R)} \quad (B-2)$$

Using $R = R_0 + h \sec \theta$ yields the approximation,

$$\ln(R/R_0) = \ln(1 + hf(r)/R_0) \approx hf(r)/R_0 = C(r)h \quad (B-3)$$

In the present work $[R/R_0]^2 \approx 1$ at $h = h_b \approx 0$, and the corresponding measured $[R/R_0]^2$ are as large as 2.0 at $h = h_t$. Thus R/R_0 ranges from 1.0 to 1.4, and $\ln(R/R_0)$ vs h approximates a straight line with maximum deviations of about 0.005. Accordingly, R^{-2} approximates an exponential in h to within about 1%. Thus, Equation B-2 may be written as

$$\begin{aligned} \epsilon(r, h) &= k e^{-\mu h f(r)} e^{-2[\ln(R_0) + \ln(R/R_0)]} \\ &= k e^{-2 \ln(R_0) - 2C(r)h - \mu f(r)h} \\ &= g(r) e^{-U(r)h}, \end{aligned} \quad (B-4)$$

where Equation B-1 has been reproduced. In terms of this

derivation, the functions $g(r)$ and $U(r)$ are

$$\begin{aligned} g(r) &= k e^{-2\ln(R_0)} \\ U(r) &= 2C(r) + \mu f(r) \end{aligned} \quad (B-5)$$

Trunnion Disk Samples

The text (Equation 4) shows that the above model yields an average radial sample efficiency of

$$\epsilon(r) = \frac{\epsilon(r, h_t) - \epsilon(r, h_b)}{\ln[\epsilon(r, h_t)/\epsilon(r, h_b)]} \quad (B-6)$$

where h_t and h_b are point source locations on the top and bottom surfaces of the trunnion disk. Detector measurements of $\epsilon(r, h)$ at both h_t and h_b for three r locations shown in Figure 5 produced the relative efficiency curves shown in Figure B-2. These curves plot $\epsilon_{rel}(r, h)$ vs E_γ for the trunnion disks, using the normalization $\epsilon_{rel}(r, h) = \epsilon(r, h)/\epsilon(0, 0)$ for each gamma energy E_γ . The $\epsilon_{rel}(r, h)$ are useful from an experimental aspect, because they are determined from the ratio of count rates and do not require knowledge of the source strength. Also, Equation B-6 may be expressed as

$$\epsilon(r) = \epsilon(0, 0) \epsilon_{rel}(r) = \epsilon(0, 0) \frac{\epsilon_{rel}(r, h_t) - \epsilon_{rel}(r, h_b)}{\ln[\epsilon_{rel}(r, h_t)/\epsilon_{rel}(r, h_b)]} \quad (B-7)$$

A BASIC code GENLDEFA was developed to calculate $\epsilon_{rel}(r)$ at the three r locations, using the curves of Figure B-2. This code also uses these $\epsilon_{rel}(r)$ to calculate the three parameters (A , B , and p) used in calculating ϵ , per modifications of Equations 5 and 6 of the main text, viz.

$$\epsilon(r) = \epsilon(0, 0) \epsilon_{rel}(r) = \epsilon(0, 0) \{A_{rel} - B_{rel} r^p\} \quad (B-8)$$

$$\epsilon = \epsilon(0, 0) \epsilon_{rel} = \epsilon(0, 0) \{A_{rel} - [2/(2+p)] B_{rel} [r_d]^p\} \quad (B-9)$$

Here, $A_{rel} = A/\epsilon(0, 0)$ and $B_{rel} = B/\epsilon(0, 0)$. Thus, GENLDEFA calculated ϵ_{rel} as a function of E_γ for the trunnions. To obtain $\epsilon(0, 0)$ as a function of E_γ , earlier calibrations with aqueous vials were used as explained below.

Aqueous vials of 65 mm diameter had been calibrated earlier

as a function of height for $E_\gamma = 88-1836$ keV using NIST-traceable standards. The ϵ were calculated for aqueous samples with h equal to that of the calibration trunnions, but the aqueous disk radius r_d and attenuation μ differed from those of the trunnions. Nevertheless, the $\epsilon(0,0)$ were obtained from these earlier aqueous vial calibrations as follows. Measurements were mapped for $\epsilon(r,h) = \epsilon_0(r,h)$ at the same locations as earlier, but with no sample (essentially air, using a thin plastic shell "sample"). Dividing the earlier $\epsilon(r,h)$ measurements for the trunnions by these yielded

$$\epsilon(r,h)/\epsilon_0(r,h) = e^{-[U(r)-U_0(r)]h} = e^{-\mu f(r)h} \quad (B-10)$$

from Equations B-4 and B-5, since $U_0(r)$ effectively has a $\mu = 0$. The μ for the trunnion was obtained from tabulations⁷, h (actually $h_t - h_b$) was measured, and $\epsilon(r,h)/\epsilon_0(r,h)$ were measured, so that the $f(r)$ could be determined. Then, obtaining the μ_A for the aqueous samples from tabulations⁷, the corresponding $\epsilon_A(r,h)$ were calculated per rearrangement of Equation B-10 as

$$\epsilon_A(r,h) = \epsilon_0(r,h) e^{-\mu_A f(r)h} \quad (B-11)$$

Thus, replacing $\epsilon(r,h)$ with $\epsilon_A(r,h)$ beginning with Equation B-6 and proceeding to Equation B-9 as before, we obtain

$$\epsilon_A = \epsilon(0,0) \epsilon_{Arel} = \epsilon(0,0) (A_{Arel} - [2/(2+p)] B_{Arel} [r_{Ad}]^{pA}) \quad (B-12)$$

where the GENLDEFA code only yields ϵ_{Arel} . However, ϵ_A are known from the earlier aqueous calibrations, so that the $\epsilon(0,0)$ are readily calculated. Subsequently, the final trunnion ϵ were determined from

$$\epsilon = \epsilon(0,0) \epsilon_{rel} = [\epsilon_A/\epsilon_{Arel}] \epsilon_{rel} = [\epsilon_{rel}/\epsilon_{Arel}] \epsilon_A \quad (B-13)$$

where the calculated ratio of the relative efficiencies is multiplied by the known efficiency of the aqueous standards. Figure B-3 shows the curves for ϵ_{rel} and ϵ_{Arel} generated from the base data of Figure B-2, and Figure B-4 shows corresponding curves for ϵ and ϵ_A .

Substituting $\epsilon(0,0)$ with the 661.6 keV gamma point-source efficiencies from ^{137}Cs standard atop the 20% and 25% HPGe detectors, Equation 12 yielded efficiencies ϵ_A in 5% agreement with the earlier measured aqueous efficiencies, as shown in Table B-1. Because the NIST-based ϵ were considered more accurate,

these were adopted over the point source values. Trunnion calculations with ϵ using Equation B-13 differed by a factor of 1.070 ± 0.020 for the two detectors, in examining the most intense 834.8 keV gamma of ^{54}Mn . Consequently, the efficiencies of these similar detectors were adjusted by factors of $(1.07)^{1/2}$ so that their individual results would agree with their average.

The above efficiency development is favored over other alternatives for several reasons in addition to being NIST-based. Table B-2 shows the results of various obvious alternatives including the adopted one. Note that the ^{54}Mn for the slab-determined RHG disk and the adjacent RHF disk agree best with the adopted method. Because the efficiency corrections for the slab samples of the RHG disk are relatively minor, the ^{54}Mn estimate for this disk is considered fairly reliable. Thus, the adopted method provides the best overall self-consistency.

The 90% HPGe was out-of-service during these calibration studies, but an efficiency curve for it was later "bootstrapped" from the other two detectors by comparing count rates for common trunnion samples; earlier calibration files for this detector were also used. The 834.8 keV gamma from Mn-54 was the main gamma used to normalize the calibrations in the range where most sample gammas (from 810.8 to 1332.6 keV) were detected. The shape of the calibration curve in this region is also only weakly affected by sample attenuation and geometry, allowing an earlier unattenuated calibration curve to check the consistency of some of the less intense gammas in this region. The intensity of the previously measured 122.0 keV gamma of ^{57}Co was sufficiently accurate ($\pm 4.7\%$) to guide the calibration at lower energies, which included other sample gammas at 136.7 keV (^{57}Co) and 320.0 keV (^{51}Cr), which have generally intensity accuracies above 25%. A gamma at 477.0 keV (^7Be) will have the least accurate efficiency, but it is not positively detected. The 90% HPGe was primarily incorporated to check whether any smaller activities were missed with the less efficient detectors. Thus, the accuracy of this efficiency curve is more than sufficient to analyze any previously undetected weak gamma peaks, whose counting errors will overshadow the accuracy of the efficiency curve. The efficiency curve is given in Figure B-5, and it was cross-calibrated using the RHR trunnion sample.

As implied in Table B-1, the above base calibrations applied to specific trunnion pieces. The h for the different trunnions ranged from 10-21 mm, but most were in the neighborhood of 20 mm. For those with $h \approx 20\text{mm}$, a perturbation correction for the small δh differences was applied, whereby the fractional change was estimated with an $\epsilon(r, h)$ of Equation B-1 approximated with an average $U(r) = U$. The count rate c_s and c_x of the standard trunnion ($h_t - h_b = h_s$) and a nearly identical one ($h_t - h_b = h_s + \delta h$) are ratioed for the correction

$$c_x/c_s = (1 - e^{-U(h_s + \delta h)}) / (1 - e^{-U h_s}) \quad (B-14)$$

which ranged from 0.972 to 1.043 for the trunnions that were corrected for small δh , as shown in Table B-3. Dividing the observed countrates by these factors normalized the countrate to that of a standard trunnion. Then the resulting activity was divided by the corresponding mass of the trunnion standard to obtain the specific activity in pCi/kg.

For trunnions with significant δh , a more elaborate correction was developed. The above method calculates an average radial efficiency $\epsilon(r)$ according to Equation B-6, which includes a term

$$\epsilon(r, h_t) / \epsilon(r, h_b) = \exp [-U(r)(h_t - h_b)] \quad (B-15)$$

Thus, for a different thickness of sample such that $h_t = h_x$, we may write

$$\begin{aligned} \epsilon(r, h_x) / \epsilon(r, h_b) &= \exp [-U(r)(h_x - h_b)] = \exp [-U(r)(h_t - h_b)X] = \\ &= [\epsilon(r, h_t) / \epsilon(r, h_b)]^X = F_{tb}(X) \end{aligned} \quad (B-16)$$

The $\epsilon(r) = \epsilon_x(r)$ corresponding to h_x is then calculated using Equation B-6 per substitution from Equation B-16, viz.

$$\epsilon_x(r) = \frac{\epsilon(r, h_x) - \epsilon(r, h_b)}{\ln[\epsilon(r, h_x) / \epsilon(r, h_b)]} = \frac{\epsilon(r, h_b) [F_{tb}(X) - 1]}{X \ln[\epsilon(r, h_t) / \epsilon(r, h_b)]} \quad (B-17)$$

Thus, this efficiency was used, where X is the thickness of the sample in units of $h = h_t - h_b$ for the reference standard. The GENLDEFC code, developed from the GENLDEFA code, calculated the corresponding efficiency ϵ_x along with the ϵ of the standard trunnion, so that the efficiency corrections ϵ_x/ϵ could be applied to these samples.

Small Layer and Slab Samples

All layer and slab samples were counted on the 90% HPGe. For these samples $\epsilon(r, h)$ was found to be sufficiently modeled as

$$\epsilon(r, h) = \epsilon(r, h_b) e^{-U(h - h_b)} \quad (B-18)$$

which is Equation 7 of the main text. Source mappings across the top of the detector produced $\epsilon(r, h_p)$ that could be fitted with the function

$$\epsilon(r, h_p) = \epsilon(r, 0) = \epsilon(0, 0) (1 + ar^3)^{-1/2}, \quad (B-19)$$

where $h_p = 0$ has been defined for convenience and a is a constant. Figure B-5 gives $\epsilon(0, 0)$, which is the point source efficiency curve for this detector. Experimental plots for the $(1 + ar^3)^{-1/2}$ dependence are given in Figure B-6. The average of $\epsilon(r, h)$ over the surface or r , depends only on $\epsilon(r, 0)$, and thus the area average over the sample is

$$\epsilon(h) = \langle \epsilon(r, 0) \rangle e^{-Uh} = \epsilon(0, 0) e^{-Uh} \langle (1 + ar^3)^{-1/2} \rangle \quad (B-20)$$

A BASIC code PLATEFF3 was written to numerically perform the average over the rectangular areas.

To average over the height of the sample for different energies, U must be calculated from

$$U = c + \mu f \quad (B-21)$$

This is the same as Equation 9 of the main text, where it was discussed that 661 and 1332 keV point sources measured two different U , which are associated with corresponding tabulated μ , and thus provide two equations for solving the two unknowns c and f . The resulting μf term dominated over the c term of U . With U known, the average over h yields

$$\epsilon = \epsilon(0, 0) \langle (1 + ar^3)^{-1/2} \rangle \frac{1 - e^{-U(ht-hb)}}{U (h_t - h_b)} \quad (B-22)$$

The layer efficiencies were directly calculated with this equation.

The method for the exponential average factor was checked experimentally with ^{54}Mn and ^{57}Co sources and a trunnion slab. The 835 keV gamma of ^{54}Mn yielded 0.833 for this factor, which is in excellent agreement with that of 0.827 for the method. The 122 keV gamma yielded a factor of 0.649, which agreed poorly with the 0.500 predicted by the method; thus, the experimental factors were applied for ^{57}Co . Note that the ^{54}Mn predictions were by interpolation, while the ^{57}Co was an extrapolation. Except for ^{57}Co , all slab-sample radionuclides were determined by the more reliable interpolation.

The ϵ for steel trunnion layers were calculated for the 835 keV gamma of ^{54}Mn and the 122 keV of ^{57}Co . Only ^{46}Sc was detected in the vanadium samples and its low level 889 keV and 1120 keV gammas were corrected assuming an average energy of 1000 keV. Only ^{22}Na was detected in the aluminum sample, and its 1274 keV gamma was used; however, a significant summing correction needed to be addressed as discussed next below.

In ^{22}Na decay, the 1274 keV gamma is coincident with a positron emission about 90% of the time, so that an average of 1.811 annihilation 511 keV gammas cascade with each 1274 keV gamma. Simultaneous detection (or summing) of 511 keV and 1274 keV gammas does not register a count in the 1274 keV spectral peak, so that the resulting peak area is abnormally low. Given that a 1274 keV gamma is detected, the probability that it sums with a 511 keV gamma is $1.811 \epsilon_T(511)$, where $\epsilon_T(511)$ is the total detection efficiency (not just peak efficiency) of the 511 keV gamma. Thus,

$$^{22}\text{Na Summing Correction} = \frac{1}{1 - 1.811 \epsilon_T(511)} \quad (\text{B-23})$$

This work calculated a summing correction for a point source atop the 90% HPGe detector. A sizeable summing correction of 1.97 resulted, which incorporated an $\epsilon_T(511) = 0.272$ from detector model calculations. The summing was also examined with point source measurements, yielding a correction of 1.87 ± 0.07 . The BASIC code DETOTEFF was developed for the calculation, which also predicted a peak ratio (511 keV/1274 keV) of 4.76 that agrees well with the average measured ratio of 4.62 ± 0.12 . From the above, a correction of 1.90 was adopted for the point source correction or $\epsilon_T(511) = 0.262$; the actual source is extended, resulting in calculated relative efficiency reductions by 0.84, and 0.73 for surface distribution and sample attenuation. Thus, for the actual sample, $\epsilon_T(511) = (0.84)(0.73)(0.262) = 0.161$, and the corresponding summing correction is 1.41. *per U.*

Mathematical Aspects of Exponential Average

Because the exponential average is frequently used in this study, its functional behavior is worth examining. Figure B-7 plots the most relevant aspects, where exponential average of 1 and x is given as $y = (x-1)/\ln(x)$, which is appropriate for comparing relative efficiencies in the present work. In the figure, the straight average $(x+1)/2$ is also plotted for comparison to emphasize the difference; use of a straight average in the present work will overestimate the efficiencies and accordingly underestimate the sample activities. Finally the percent deviations in y that result from percent deviations in x

are examined. Fortunately, the x-deviations produce relatively smaller y-deviations, allowing some leniency in the experimental measurements of x. Thus, the accuracy of the average relative efficiency from plots like that of Figure B-2 produce exponential averages that are considerably more accurate.

Further Information

The present appendix provides essential data for comparison with other LDEF results. Further information such data files, calculation codes, detailed detector dimensions, and individual geometry and attenuation correction factors can be provided upon special request.

Table B-1. Trunnion Calibrations

Test of Model with Standard Vial

For the 20% and 25% HPGe detectors, calibrations based on NIST standards were also available for soil and aqueous standards [ref 6]. The largest vial for these standards had diameter of 65 mm, which is somewhat smaller than the diameter of 82 mm for the trunnion samples. The model given by Equation B-12 was tested as summarized below:

Detector	Sample diam x ht	661.6 keV Efficiency /Water		
		NIST	Model	%-diff
20% HPGe	65mm x 19.6mm	0.0132	0.0139	5.3 %
25% HPGe	65mm x 18.1mm	0.0171	0.0179	4.7 %

The agreement is quite good, but suggests a systematic error of about 5% for the model.

Model Normalization to NIST Standards

To address the above 5% bias, the trunnion efficiency curves were developed as

$$\epsilon_T = \epsilon(\text{Water Vial}|\text{NIST}) \frac{\epsilon(\text{Trunnion Sample}|\text{Model})}{\epsilon(\text{Water Vial}|\text{Model})}$$

where any bias in the model of tends to be cancelled in the ratio.

Normalization to Trunnion Average for 20% and 25% HPGe

The model for ϵ_T above yielded activities that differed by a factor of 1.070 ± 0.020 for the two detectors. Thus, the geometric average of the results would be $(1.07)^{1/2}$ larger for one detector and $(1.07)^{-1/2}$ smaller for the other. Accordingly, correcting each detector to agree with the average yielded

$$\begin{aligned} \epsilon(20\% \text{ HPGe}) &= (1.07)^{1/2} \epsilon_T(20\% \text{ HPGe}) = 1.034 \epsilon_T(20\% \text{ HPGe}) \\ \epsilon(25\% \text{ HPGe}) &= (1.07)^{-1/2} \epsilon_T(25\% \text{ HPGe}) = 0.967 \epsilon_T(25\% \text{ HPGe}) \end{aligned}$$

Table B-2. Alternative Efficiency Development

Efficiency Method	Cs-137 Efficiency		Trunnion Mn-54	
	Det #1 (25% HPGe)	Det #2 (20% HPGe)	RHGslabs	RHFdisk
Measurements				
$\epsilon(\text{NIST}) = \epsilon_n$	0.0171	0.0131	-	-
$\epsilon(\text{Pt Std}) = \epsilon_s$	0.0179	0.0139	-	-
Adopted				
$\epsilon_n(1.07)^{\pm 1/2}$	0.0165	0.0135	79.8	78.98 $\pm$ 1.34
Alternatives				
$\epsilon_n(\#1) \ 1.07 \times \epsilon_n(\#2)$	0.0171	0.0137	79.8	76.35 $\pm$ 1.30
$\text{Avg}(\epsilon_n, \epsilon_s) (1.07)^{\pm 1/2}$	0.0169	0.0140	79.8	76.69 $\pm$ 1.30
$\epsilon_s(1.07)^{\pm 1/2}$	0.0173	0.0142	79.8	75.22 $\pm$ 1.28

Table B-3. Corrections for Count Rate

c_x/c_s = count rate ratio of unknown/standard samples with same uniform activity density

Detector/Energy	ID h(mm)	Sample					
		LHP 18.1	RHP 18.5	RHR 18.5	RHS 18.8	LHS 19.6	LHR 20.6
#1(25%HPGe)/122		=1.000	1.000	1.000	1.000	1.000	1.000
/661-		=1.000	1.008	1.008	1.013	1.028	1.043
/1332							
#2(20%HPGe)/122		1.000	1.000	1.000	1.000	=1.000	1.000
/661-		0.972	0.980	0.980	0.986	=1.000	1.015
1332							
#3(90%HPGe)/122		1.000	1.000	=1.000	1.000	1.000	1.000
/661-		0.992	1.000	=1.000	1.006	1.020	1.035
1332

Figure B-1. Geometrical Relations for Sample Attenuation

DETECTOR #1

Figure B-2a. $\epsilon_{rel}(r, h) = \epsilon_r(r, h)$ Plots for 25% HPGe

DETECTOR #2

Figure B-2b. $\epsilon_{rel}(r, h) = \epsilon_r(r, h)$ Plots for 20% HPGe.

DETECTOR #1

Figure B-3a. $\epsilon_{\text{rel}}(\text{H}_2\text{O})$ and $\epsilon_{\text{rel}}(\text{LHP})$ Plots for 25% HPGe.

Figure B-3b. $\epsilon_{\text{rel}}(\text{H}_2\text{O})$ and $\epsilon_{\text{rel}}(\text{LHS})$ Plots for 20% HPGe.

DETECTOR #1

Figure B-4a. $\epsilon(\text{H}_2\text{O})$ and $\epsilon(\text{LHP})$ Plots for 25% HPGe.

DETECTOR #2

Figure B-4b. $\epsilon(\text{H}_2\text{O})$ and $\epsilon(\text{LHS})$ Plots for 20% HPGe.

DETECTOR #3

Figure B-5. Efficiency Curves for 90% HPGe

Figure B-6. Relative Efficiency on Surface of 90% HPGe

The efficiency radial dependence is examined in terms of the empirical efficiency factor $F = (1 + ar^3)^{-1/2}$. Calculations for the average $F = \langle F \rangle$ for the maximum 2"x2" slabs of this study are given, along with the fitted values of a .

Figure B-7. Exponential Average Comparisons

The the average of 1 and x are examined as an exponential average y and straight average y_s . Also, the relative error sensitivity for the exponential average are examined as $(dy/y)/(dx/x)$.

Appendix C. Sample Details

The tables of this appendix give details concerning the LDEF samples examined at SRS. Table C-1 gives the sample labels, archival files, dimensions, mass, counting dates, and lab institutions from which the samples were received. Table C-2 summarizes the sample results and averages obtained. Each table is subdivided for (A) trunnion samples, (B) trunnion layers, and (C) vanadium and aluminum pieces. The order in the Tables parallels that of Tables 1-3 of the main text, to allow efficient cross referencing, as summarized below:

Appendix C Tables

- C-1.A Trunnion Counting Information
- C-1.B Trunnion Layer Counting Information
- C-1.C Vanadium and Aluminum Counting Information

- C-2.A Detailed Trunnion Results - 20% and 25% HPGe Detectors
- C-2.A' Detailed Trunnion Results - 90% HPGe Detector
- C-2.B Trunnion Layer Samples - 90% HPGe Detector
- C-2.C Vanadium and Aluminum Samples - 90% Detector

Table C-1.A. Trunnion Counting Information^a

<u>Sample/ Geo/Det</u>	<u>Spectrum File</u>	<u>Mass g</u>	<u>Thick mm</u>	<u>Counting 1990</u>	<u>SRS Recpt</u>	<u>Previous Laboratory</u>
LHB/A/1 /B/1	1657NASA.DAT 1669NASA.DAT	760.8 ^b	18.6	6/15-6/18 6/29-7/2	5/25	NASA/Houston TX
LHE/A/2 /B/1	1652NASA.DAT 1673NASA.DAT	430.0	10.1	6/11-6/13 7/3-7/6	6/7	TVA/Muscle Shoals AL
LHF/A/1 /B/1	1654NASA.DAT 1675NASA.DAT	715.4	17.0	6/13-6/15 7/6-7/9	6/11	LBL/Berkeley CA
LHP/A/1 /B/1 B/3	1589NASA.LHP 1591NASA.LHP 1605NASA.LHP	773	18.1	3/9-3/12 3/12-3/15 4/9-4/11	3/7	NASA/Hunts- ville AL
LHR/A/2 /B/1 /B/3	1590NASA.LHR 1593NASA.LHR 1606NASA.LHR	878	20.6	3/9-3/12 3/16-3/19 4/11-4/13	3/7	NASA/Hunts- ville AL
LHS/A/2 /B/2 /B/3	1592NASA.LHS 1594NASA.LHS 1607NASA.LHS	838	19.6	3/12-3/15 3/16-3/19 4/13-4/16	3/7	NASA/Hunts- ville AL
RHB/A/2 /B/2	1658NASA.DAT 1670NASA.DAT	696.2 ^c	17.0	6/18-6/20 6/29-7/2	5/25	NASA/Houston TX
RHE/A/1 /B/2	1651NASA.DAT 1674NASA.DAT	459.7	10.8	6/11-6/13 7/3-7/6	6/7	TVA/Muscle Shoals AL
RHF/A/2 /B/2	1655NASA.DAT 1676NASA.DAT	648.2	15.2	6/13-6/15 7/6-7/9	6/11	LBL/Berkeley CA
RHP/A/1 /B/1 /B/3	1595NASA.RHP 1599NASA.RHP 1603NASA.RHP	790.8	18.5	3/22-3/26 3/30-4/2 4/4-4/6	3/21	NASA/Hunts- ville AL
RHR/A/2 /B/2 /B/3	1596NASA.RHR 1598NASA.RHR 1601NASA.RHR	788.8	18.5	3/22-3/26 3/26-3/28 3/30-4/2	3/21	NASA/Hunts- ville AL
RHS/A/1 /B/2 /B/3	1597NASA.RHS 1600NASA.RHS 1602NASA.RHS	801.5	18.8	3/26-3/28 3/30-4/2 4/2-4/4	3/21	NASA/Hunts- ville AL

Table Notes -next page

Table C-1.A. (Continued)

Table Notes

a) Abbreviated table headings are detailed as

<u>Sample/ Geo/Det</u>	Sample label/ Geometry label facing (A) away from or (B) toward detector/ Detector is (1) 25%, (2) 20%, or (3) 90% HPGe.
----------------------------	--

<u>Spectrum File</u>	File label of ADCAM spectrum sent on floppy disk to NASA for permanent archive of LDEF studies.
--------------------------	--

<u>Mass g</u>	Measured mass of sample at SRS.
-------------------	---------------------------------

<u>Thick mm</u>	Disk thicknesses calculated using direct measurements and masses of samples, with all samples assumed to have identical diameters.
---------------------	--

<u>Counting 1990</u>	Counting interval dates - detailed live counting times are available from the disk files.
--------------------------	--

<u>SRS Recpt</u>	Date in 1990 that sample was received.
----------------------	--

<u>Previous Laboratory</u>	Laboratory from which sample was received.
--------------------------------	--

b) Sample LHB had 17 mm hole in center, and would have mass of 795 g if sample were solid.

c) Sample RHB had 17 mm hole in center, and would have mass of 727.5 g if sample were solid.

Table C-1.B. Trunnion Layer Counting Information^a

All these samples were received from NASA, Huntsville AL, on May 5, 1990. All samples were counted on 90% HPGe (Detector #3). Archival files are referenced in sub-table at bottom of page.

<u>Space Side of Trunnion</u>				<u>Earth Side of Trunnion</u>			
<u>Sample/</u> <u>Geo/Dt3</u>	<u>Mass</u> <u>g</u>	<u>Area</u> <u>inxin</u>	<u>Counting</u> <u>1990</u>	<u>Sample/</u> <u>Geo/Dt3</u>	<u>Mass</u> <u>g</u>	<u>Area</u> <u>inxin</u>	<u>Counting</u> <u>1990</u>
RH-G-SP-				RH-G-ER-			
2/A	32.9	2x2	5/21-5/23	2/A	32.7	2x2	5/23-5/25
/B			9/18-9/19	/B			9/11-9/12
3/A	51.1	2x2	6/18-6/20	3/A	51.7	2x2	6/25-6/27
/B			9/12-9/13	/B			8/1-8/3
4/A	68.4	2x2	6/22-6/25	4/A	68.3	2x1.75	6/27-6/29
/B			9/17-9/18	/B			9/10-9/11
5/A	74.5	2x2	6/20-6/22	5/A	76.0	2x1.75	6/29-7/2
/B			7/16-7/18	/B			7/18-7/20
6/A	72.5	2x1.5	6/6-6/8	6/A	72.2	2x1.5	6/8-6/11
/B			8/6-8/8	/B			7/30-8/1

Note - The sample thicknesses were calculated in g/cm² using the above data. These thicknesses were converted to cm as needed, using the trunnion density.

Sub-Table C-1.B Archival Data Files

<u>Sample/Geometry</u>	<u>Spectrum File</u>	<u>Sample/Geometry</u>	<u>Spectrum File</u>
RH-G-SP-2/A	1621NASA.DAT	RH-G-ER-2/A	1624NASA.DAT
/B	1727NASA.DAT	/B	1720NASA.DAT
3/A	1660NASA.DAT	3/A	1677NASA.DAT
/B	1721NASA.DAT	/B	1686NASA.DAT
4/A	1666NASA.DAT	4/A	1668NASA.DAT
/B	1726NASA.DAT	/B	1719NASA.DAT
5/A	1661NASA.DAT	5/A	1671NASA.DAT
/B	1679NASA.DAT	/B	1680NASA.DAT
6/A	1641NASA.DAT	6/A	1650NASA.DAT
/B	1688NASA.DAT	/B	1685NASA.DAT

a) Abbreviated table headings described in Table C-1.A notes.

Table C-1.C. Vanadium and Aluminum Counting Information^a

<u>Sample/ Geo/Dt3</u>	<u>Spectrum File</u>	<u>Mass g</u>	<u>Area inxin</u>	<u>Counting 1990/1991</u>	<u>SRS Recpt</u>	<u>Previous Laboratory</u>
<u>Vanadium</u>						
G12-A2FNV/A	1630NASA.DAT	52.4	2x2	5/29-5/31	5/24	LLL/Livermore
B	1636NASA.DAT			5/31-6/4		CA
I-C9-V/A	1653NASA.DAT	53.0	2x2	6/11-6/13	5/25	NASA/Houston
/B	1678NASA.DAT			7/12-7/16		TX
I-F2-V/A	1656NASA.DAT	53.6	2x2	6/16-6/18	6/11	LBL/Berkeley
/B	1741NASA.DAT			10/19-10/22		CA
I-H12-VA/A	1682NASA.DAT	19.4	2x3/4	7/23-7/25	7/18	PNL/Richland
/B	1731NASA.DAT			9/24-9/25		WA
I-H12-VB/A	1683NASA.DAT	19.8	2x3/4	7/25-7/27	7/18	PNL/Richland
/B	1730NASA.DAT			9/21-9/24		WA
<u>Aluminum</u>						
ESR-1/A	1672NASA.DAT	63.4	2x2	7/5-7/6	5/17	NASA/Hunts-
/B	1729NASA.DAT			9/20-9/21		ville AL
ESR-5/A	1677NASA.DAT	63.5	2x2	7/6-7/9	5/17	NASA/Hunts-
/B	1687NASA.DAT			8/3-8/6		ville AL
KP-3/A	1789NASA.DAT	65.25	2x2	1/15-1/17	1/14	NASA/Hunts-
/B	1790NASA.DAT			1/17-1/18		ville AL
KP-10/A	1791NASA.DAT	65.42	2x2	1/18-1/21	1/14	NASA/Hunts-
	1792NASA.DAT			1/21-1/22		ville AL

Note - The sample thicknesses were calculated in g/cm² using the above data. These thicknesses were converted to cm as needed, using the sample densities.

a) Abbreviated table headings described in Table C-1.A notes.

Table C-2.A. Detailed Trunnion Results - 20% and 25% HPGe Detectors

Sample Orientations:

- A. Label facing away from detector
- B. Label facing detector
- C. Average of above - $(1/\sigma^2)$ -weighted

Decay Correction Date: January 20, 1990

Sample	Isotopic Activities in pCi/Kg Sample							
	<u>Be-7</u>	<u>Sc-46</u>	<u>Cr-51</u>	<u>Mn-54</u>	<u>Co-56</u>	<u>Co-57</u>	<u>Co-58</u>	<u>Co-60</u>
LHB/A	8.68	4.46	73.99	124.54	4.54	16.02	4.48	2.58
	± 23.87	± 0.89	± 149.08	± 2.17	± 0.95	± 1.10	± 1.66	± 0.28
LHB/B	-2.17	4.20	72.91	115.88	4.64	14.49	2.22	1.52
	± 26.04	± 0.79	± 181.72	± 2.17	± 1.20	± 0.99	± 1.59	± 0.24
LHB/C	3.73	4.31	73.56	120.21	4.58	15.17	3.31	1.96
(AVG)	± 17.60	± 0.59	± 115.26	± 1.53	± 0.75	± 0.73	± 1.15	± 0.18
LHE/A	33.45	3.65	-168.39	94.74	3.95	8.17	0.21	1.53
	± 30.83	± 1.07	± 168.39	± 2.73	± 1.34	± 0.95	± 2.09	± 0.42
LHE/B	23.55	5.31	-99.64	95.53	2.41	10.93	2.12	1.65
	± 29.43	± 0.95	± 199.99	± 2.27	± 0.94	± 0.92	± 1.77	± 0.44
LHE/C	28.27	4.57	-139.87	95.21	2.92	9.60	1.33	1.59
(AVG)	± 21.29	± 0.71	± 128.81	± 1.75	± 0.77	± 0.66	± 1.35	± 0.30
LHF/A	-2.98	2.88	105.68	100.50	4.86	9.75	5.39	1.22
	± 26.78	± 0.67	± 151.12	± 1.99	± 1.20	± 1.08	± 1.72	± 0.37
LHF/B	-24.80	4.04	-74.08	100.50	4.83	10.84	2.97	1.47
	± 24.80	± 0.78	± 184.70	± 1.99	± 0.97	± 0.78	± 1.56	± 0.23
LHF/C	-14.72	3.37	33.60	100.50	4.84	10.47	4.06	1.40
(AVG)	± 18.19	± 0.51	± 116.96	± 1.41	± 0.75	± 0.63	± 1.16	± 0.19

Table C-2.A. (Continued)

Sample Orientations:

- A. Label facing away from detector
- B. Label facing detector
- C. Average of above - $(1/\sigma^2)$ -weighted

Decay Correction Date: January 20, 1990

Sample	Isotopic Activities in pCi/Kg Sample							
	<u>Be-7</u>	<u>Sc-46</u>	<u>Cr-51</u>	<u>Mn-54</u>	<u>Co-56</u>	<u>Co-57</u>	<u>Co-58</u>	<u>Co-60</u>
LHP/A	-5.79 ±5.67	3.37 ±.36	26.00 ±11.32	79.93 ±1.31	2.44 ±.39	8.36 ±.60	5.06 ±.61	1.29 ±.21
LHP/B	2.41 ±6.03	3.27 ±.39	12.05 ±12.05	79.14 ±1.31	2.96 ±.42	9.20 ±.63	4.00 ±.64	1.75 ±.23
LHP/C (AVG)	-1.94 ±4.13	3.32 ±.27	19.46 ±8.25	79.53 ±.93	2.68 ±.29	8.77 ±.44	4.56 ±.44	1.51 ±.16
LHR/A	-6.97 ±6.15	3.70 ±.38	53.13 ±13.03	77.27 ±1.45	2.85 ±.41	6.41 ±.60	4.75 ±.66	1.61 ±.24
LHR/B	-8.79 ±6.13	3.70 ±.40	15.65 ±12.92	78.27 ±1.26	2.75 ±.43	8.47 ±.64	4.40 ±.63	1.45 ±.22
LHR/C (AVG)	-7.88 ±4.34	3.70 ±.28	34.23 ±9.17	77.84 ±.95	2.80 ±.30	7.37 ±.44	4.57 ±.46	1.52 ±.16
LHS/A	7.59 ±6.55	4.16 ±.44	24.44 ±13.22	76.16 ±1.47	2.67 ±.45	6.17 ±.59	4.73 ±.69	1.88 ±.25
LHS/B	-0.83 ±6.97	4.74 ±.45	23.93 ±14.80	75.03 ±1.36	3.28 ±.47	5.54 ±.86	5.80 ±.71	1.45 ±.25
LHS/C (AVG)	3.64 ±4.77	4.44 ±.32	24.21 ±9.86	75.55 ±1.00	2.96 ±.33	5.97 ±.49	5.25 ±.50	1.66 ±.18

Table C-2.A. (Continued)

Sample Orientations:

- A. Label facing away from detector
- B. Label facing detector
- C. Average of above - $(1/\sigma^2)$ -weighted

Decay Correction Date: January 20, 1990

Sample	Isotopic Activities in pCi/Kg Sample							
	Be-7	Sc-46	Cr-51	Mn-54	Co-56	Co-57	Co-58	Co-60
RHB/A	18.18	5.10	170.11	83.59	3.40	8.16	4.76	1.20
	±29.99	±1.06	±189.02	±2.20	±1.12	±0.91	±1.99	±0.33
RHB/B	56.34	4.53	117.01	81.85	3.03	6.76	4.61	1.63
	±25.45	±3.02	±195.32	±1.74	±1.11	±0.77	±1.65	±0.38
RHB/C	40.37	5.04	144.43	82.52	3.21	7.34	4.67	1.39
(AVG)	±19.40	±1.00	±135.83	±1.36	±0.79	±0.59	±1.27	±0.25
RHE/A	2.28	2.06	205.54	81.26	2.02	9.82	1.19	0.75
	±25.11	±0.89	±146.82	±2.34	±1.19	±0.98	±1.70	±0.29
RHE/B	14.90	1.71	-317.25	78.57	2.39	4.99	3.84	1.63
	±29.13	±1.37	±211.72	±2.10	±1.57	±0.70	±1.92	±0.32
RHE/C	7.66	1.96	35.78	79.77	2.15	6.63	2.35	1.16
(AVG)	±19.02	±0.75	±120.65	±1.57	±0.95	±0.57	±1.27	±0.22
RHF/A	45.21	2.47	-88.77	77.42	3.23	6.63	3.15	1.15
	±30.42	±0.97	±177.53	±2.25	±1.32	±0.91	±1.98	±0.32
RHF/B	49.32	3.50	199.32	79.84	4.19	7.26	1.97	1.43
	±27.13	±0.91	±199.32	±1.67	±1.20	±0.78	±1.64	±0.26
RHF/C	47.50	2.99	38.68	78.98	3.75	7.00	2.45	1.32
(AVG)	±20.25	±0.64	±132.57	±1.34	±0.89	±0.59	±1.26	±0.20

Table C-2.A. (Continued)

Sample Orientations:

- A. Label facing away from detector
- B. Label facing detector
- C. Average of above - $(1/\sigma^2)$ -weighted

Decay Correction Date: January 20, 1990

Sample	Isotopic Activities in pCi/Kg Sample							
	<u>Be-7</u>	<u>Sc-46</u>	<u>Cr-51</u>	<u>Mn-54</u>	<u>Co-56</u>	<u>Co-57</u>	<u>Co-58</u>	<u>Co-60</u>
RHP/A	0.24 ±5.98	2.88 ±.35	29.14 ±13.40	72.12 ±1.17	2.93 ±.38	8.35 ±.55	4.92 ±.59	1.64 ±.20
RHP/B	-2.27 ±7.54	3.84 ±.45	17.47 ±18.47	74.08 ±1.30	2.31 ±.48	8.36 ±.69	2.82 ±.71	1.55 ±.23
RHP/C (AVG)	-0.73 ±4.69	3.24 ±.27	25.12 ±10.85	72.99 ±.87	2.69 ±.30	8.36 ±.43	4.07 ±.45	1.60 ±.15
RHR/A	10.29 ±6.37	3.72 ±.37	46.55 ±16.09	72.86 ±1.27	1.89 ±.39	5.76 ±.52	3.88 ±.65	1.46 ±.22
RHR/B	-3.82 ±9.55	3.79 ±.56	27.66 ±22.45	72.63 ±1.73	2.93 ±.57	6.24 ±.71	4.93 ±.94	1.17 ±.27
RHR/C (AVG)	5.95 ±5.30	3.74 ±.31	40.14 ±13.08	72.78 ±1.03	2.22 ±.32	5.93 ±.42	4.22 ±.54	1.34 ±.17
RHS/A	3.45 ±8.33	3.89 ±.47	32.76 ±19.14	73.19 ±1.56	3.36 ±.54	7.67 ±.77	4.17 ±.78	1.61 ±.28
RHS/B	-1.37 ±8.12	3.88 ±.47	48.42 ±20.76	74.14 ±1.38	2.27 ±.50	5.00 ±.60	4.91 ±.79	1.19 ±.23
RHS/C (AVG)	0.98 ±5.82	3.89 ±.33	39.96 ±14.07	73.72 ±1.03	2.77 ±.37	6.00 ±.47	4.54 ±.56	1.36 ±.18

Table C-2.A'. Detailed Trunnion Results - 90% HPGe Detector

Sample Orientation - Label facing toward detector.

Decay Correction Date - January 20, 1990

<u>Sample</u>	<u>Isotopic Activities in pCi/Kg Sample</u>							
	<u>Be-7</u>	<u>Sc-46</u>	<u>Cr-51</u>	<u>Mn-54</u>	<u>Co-56</u>	<u>Co-57</u>	<u>Co-58</u>	<u>Co-60</u>
LHP	6.01 ±5.46	3.78 ±.29	3.94 ±16.55	79.32 ±1.01	2.61 ±.31	6.53 ±.37	5.35 ±.50	1.64 ±.15
LHR	-6.51 ±6.74	3.91 ±.34	35.00 ±21.44	75.54 ±.97	2.47 ±.35	6.93 ±.65	4.84 ±.53	1.53 ±.15
LHS	1.58 ±4.52	4.28 ±.25	20.82 ±14.50	75.09 ±.73	2.28 ±.24	6.32 ±.30	4.73 ±.37	1.50 ±.11
RHP	13.37 ±5.37	3.79 ±.33	55.21 ±15.26	71.99 ±1.00	2.63 ±.33	6.25 ±.42	4.77 ±.49	1.26 ±.16
RHR	10.17 ±3.77	3.32 ±.24	17.36 ±10.38	72.73 ±.75	2.50 ±.24	6.33 ±.30	4.33 ±.36	1.64 ±.11
RHS	3.86 ±4.88	4.00 ±.32	23.39 ±14.44	75.52 ±.99	2.69 ±.33	6.02 ±.42	4.06 ±.62	1.51 ±.16

Table C-2.B. Trunnion Layer Samples - 90% HPGe Detector

Sample Measurements:

- A. Label facing away from detector
- B. Label facing detector
- C. Weighted Average of (A,B) - $(1/\sigma^2)$ -weighted
- D. Direct Average of (A,B) - even-weighted

Decay Correction Date: January 20, 1990

<u>Space Side of Trunnion</u>			<u>Earth Side of Trunnion</u>		
<u>Sample</u>	<u>pCi/Kg Sample</u>		<u>Sample</u>	<u>pCi/Kg Sample</u>	
<u>RH-G-SP-</u>	<u>Mn-54</u>	<u>Co-57</u>	<u>RH-G-ER-</u>	<u>Mn-54</u>	<u>Co-57</u>
2/A	92.29 ±3.65	17.17 ±2.55	2/A	105.39 ±3.65	21.19 ±2.98
2/B	94.92 ±5.84	21.96 ±5.80	2/B	91.53 ±6.20	13.81 ±4.03
2/C	95.18 ±3.10	17.95 ±2.33	2/C	101.83 ±3.14	18.58 ±2.40
2/D	95.10 ±3.44	19.57 ±3.17	2/D	98.46 ±3.60	17.50 ±2.51
3/A	89.38 ±3.07	14.52 ±2.05	3/A	98.05 ±2.69	15.40 ±2.25
3/B	77.10 ±4.60	15.05 ±3.15	3/B	89.20 ±3.08	14.63 ±2.52
3/C	85.60 ±2.55	14.68 ±1.72	3/C	94.21 ±2.03	15.06 ±1.68
3/D	83.24 ±2.77	14.78 ±1.88	3/D	93.62 ±2.04	15.02 ±1.69

Table C-2.B. (Continued)
(See notes on preceding page)

<u>Space Side of Trunnion</u>			<u>Earth Side of Trunnion</u>		
<u>Sample</u>	<u>pCi/Kg Sample</u>		<u>Sample</u>	<u>pCi/Kg Sample</u>	
<u>RH-G-SP-</u>	<u>Mn-54</u>	<u>Co-57</u>	<u>RH-G-ER-</u>	<u>Mn-54</u>	<u>Co-57</u>
4/A	79.63 ±2.10	12.82 ±1.39	4/A	91.87 ±2.43	16.79 ±1.86
4/B	75.61 ±4.02	11.14 ±3.15	4/B	83.78 ±4.05	18.17 ±4.02
4/C	78.82 ±1.80	12.55 ±1.27	4/C	89.73 ±2.08	17.03 ±1.69
4/D	77.62 ±2.25	11.98 ±1.72	4/D	87.82 ±2.36	17.48 ±2.22
5/A	73.95 ±2.04	11.16 ±1.61	5/A	83.31 ±2.07	12.17 ±1.36
5/B	67.82 ±2.04	13.21 ±1.96	5/B	76.68 ±2.07	9.67 ±1.95
5/C	70.89 ±1.44	11.99 ±1.25	5/C	80.00 ±1.47	11.35 ±1.12
5/D	70.89 ±1.44	12.18 ±1.27	5/D	80.00 ±1.47	10.92 ±1.19
6/A	72.35 ±2.09	11.27 ±1.78	6/A	79.36 ±2.09	13.05 ±1.44
6/B	68.17 ±2.51	14.21 ±2.24	6/B	73.93 ±2.51	11.09 ±1.96
6/C	70.64 ±1.61	12.40 ±1.39	6/C	77.13 ±1.60	12.36 ±1.16
6/D	70.26 ±1.63	12.74 ±1.43	6/D	76.64 ±1.63	12.07 ±1.22

Table C-2.C. Vanadium and Aluminum Samples - 90% HPGe Detector

Sample Measurements:

- A. Label facing away from detector
- B. Label facing detector
- C. Weighted Average of (A,B) - $(1/\sigma^2)$ -weighted
- D. Direct Average of (A,B) - even-weighted

Decay Correction Date: January 20, 1990

<u>Vanadium Samples</u>		<u>Aluminum Samples</u>	
<u>Sample</u>	<u>pCi/Kg Sample</u>	<u>Sample</u>	<u>pCi/Kg Sample</u>
	<u>Sc-46</u>		<u>Na-22</u>
G12-A2-FNV/A	16.44 ±1.34	ESR-1/A	88.40 ±4.94
G12-A2-FNV/B	15.55 ±2.27	ESR-1/B	92.79 ±4.39
G12-A2-FNV/C	16.21 ±1.16	ESR-1/C	90.85 ±3.28
G12-A2-FNV/D	16.00 ±1.32	ESR-1/D	90.60 ±3.31
I-C9-V/A	18.58 ±2.24	ESR-5/A	93.34 ±2.75
I-C9-V/B	21.90 ±2.02	ESR-5/B	90.05 ±2.75
I-C9-V/C	20.41 ±1.50	ESR-5/C	91.70 ±1.94
I-C9-V/D	20.24 ±1.51	ESR-5/D	91.70 ±1.94

Table C-2.C. (Continued)
(See notes on preceding page)

<u>Vanadium Samples</u>		<u>Aluminum Samples</u>	
<u>Sample</u>	<u>pCi/Kg Sample</u>	<u>Sample</u>	<u>pCi/Kg Sample</u>
	<u>Sc-46</u>		<u>Na-22</u>
I-F2-V/A	18.19 ±2.54	KP-3/A	113.13 ±2.76
I-F2-V/B	24.06 ±4.75	KP-3/B	109.82 ±2.76
I-F2-V/C	19.49 ±2.24	KP-3/C	111.47 ±1.95
I-F2-V/D	21.12 ±2.70	KP-3/D	111.47 ±1.95
I-H12-VA/A	24.07 ±7.73	KP-10/A	80.57 ±2.76
I-H12-VA/B	15.57 ±24.49	KP-10/B	70.08 ±4.41
I-H12-VA/C	23.30 ±7.37	KP-10/C	77.62 ±2.34
I-H12-VA/D	19.82 ±12.84	KP-10/D	75.33 ±2.60
I-H12-VB/A	27.59 ±7.13		
I-H12-VB/B	15.58 ±11.51		
I-H12-VB/C	24.26 ±6.06		
I-H12-VB/D	21.59 ±6.77		

**DATE
FILMED**

5/04/92