LOT NO. 1 OF FRIT 202 FOR DWPF COLD RUNS (U)

by

R. F. Schumacher

Westinghouse Savannah River Company

Savannah River Site

Aiken, South Carolina 29808

DOE Contract No. **DE-AC09-89SR18035**

This paper was prepared in connection with work done under the above contract number with the U. S. Department of Energy. By acceptance of this paper, the publisher and/or recipient acknowledges the U. S. Government's right to retain a nonexclusive, royalty-free license in and to any copyright covering this paper, along with the right to reproduce and to authorize others to reproduce all or part of the copyrighted paper.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615) 576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

WESTINGHOUSE SAVANNAH RIVER CO.
SAVANNAH RIVER TECHNOLOGY CENTER

WSRC-TR-92-569
Revision 0

Keywords: DWPF, WAPS,
glass frit, analyses
Retention Time: Permanent

CC E.W. Holtzscheiter, 773-A
N.E. Bibler, 773-A
J.T. Carter, 704-T
L.F. Landon, "
C.T. Randall, "
N.D. Hutson, "
K.G. Brown, "
J.F. Sproull, 704-S
S.L. Marra, 704-S
H. Moore, 704-S
L.J. Jones, 704-27S
B. Latrace, BH-313
Glass Tech, (10)
DC&RM, 773-52A (4)

To: M.J. Plodinec, 773-A
From: R.F. Schumacher, 773-42A

April 1, 1993

R.F. Schumacher
4-1-93

Lot No.1 of Frit 202 for DWPF Cold Runs - (U)

SUMMARY

The following report was prepared at the end of 1992 and summarizes the evaluation of the first lot sample of DWPF Frit 202 from Cataphote Inc. Publication of this report was delayed until the results from the carbon analyses could be included. To avoid confusion the frit specifications presented in this report were those available at the end of 1992. The specifications were slightly modified early in 1993.

The frit was received and evaluated for moisture, particle size distribution, organic-inorganic carbon and chemical composition. Moisture content and particle size distribution were determined on a representative sample at SRTC. These properties were within the DWPF specifications for Frit 202. A representative sample was submitted to Corning Engineering Laboratory Services for chemical analyses. The sample was split and two dissolutions prepared. Each dissolution was analyzed on two separate days. The results indicate that there is a high probability (>95%) that the silica content of this frit is below the specification limit of 77.0 ± 1.0 wt%. The average of the four analyzed values was 75.1 wt% with a standard deviation of 0.28 wt%. All other oxides were within the elliptical two sigma limits. Control standard frit samples were submitted and analyzed at the same time and the results were very similar to previous analyses of these materials.

DWPF Lot 1 was very similar to the Cataphote qualification sample which was also low in silica. However, this material was outside the elliptical band of acceptability. The vendor was notified that the material was not acceptable for DWPF cold runs but would be usable at TNX. All other measurements were within specification.

INTRODUCTION

In the DWPF, glass forming chemicals will be added to the waste in the form of premelted glass frit¹. On an oxide weight basis, DWPF glass will consist of approximately 64 wt% glass frit, 8 wt% precipitate hydrolysis aqueous product, and 28 wt% sludge. The glass frit and the precipitate hydrolysis aqueous product together make up what is called the glass-former composition. Glass Frit 202 was developed to provide a glass which is processable in the DWPF melter, compatible with a wide variety of projected waste types, and produces a waste form which has acceptable leach resistance.

The Waste Acceptance Preliminary Specifications, (WAPS)² require that the DWPF control the consistency of the waste glass product. As described in the Waste Form Compliance Plan (WCP)³, this will be achieved through control of the chemical composition of the glass product. Since the glass frit purchased by DWPF will constitute approximately two thirds of the glass product, control of the composition of the frit is an important part of meeting the WAPS. Current plans are to control the composition of the frit through the procurement specifications⁴ and chemical analyses of representative lot samples. A summary of the chemical and physical specifications for Frit 202 is presented in Table 1.

Table 1
Chemical and Physical Specification Frit 202 (Dec.1992)

Component	Concentration (wt%)
SiO ₂	77.0 ± 1.0
Na ₂ O	6.0 ± 0.5
B ₂ O ₃	8.0 ± 0.5
Li ₂ O	7.0 ± 0.5
MgO	2.0 ± 0.25
Major Components	Sum of Above
Chemical	Maximum (wt%)
Al	1.0
Fe	0.2
Mn	0.2
Ni	0.2
Cr	0.1
Pb	0.1
Ti	0.15
F	0.05
Cl	0.05
Total Undesirable Component	2.25 (As Oxides)

Total undesirable components is equal to 100 minus the actual analysis of the major oxide components as listed in Table 1 and includes but is not limited to Al, Fe, Mn, Ni, Cr, Pb, Ti, F, Cl. Additional undesirable components > 0.05 wt% shall be reported along with their amount in the certificate of conformance. The moisture content of each lot of material shall be less than 0.1 wt%. The equivalent carbon as measured by a Chemical Oxygen Demand (COD) shall be less than 0.1 wt% equivalent carbon. The particle size distribution of each lot of frit must be such that greater than or equal to 99.0 wt% passing through a Tyler 80 mesh screen, and less than 10 wt% passing through a Tyler 200 mesh screen. [Note: The Tyler and U.S. Standard are equivalent at 80 and 200 mesh openings.] The material must be free flowing.

A qualification sample of Cataphote Frit⁵ was evaluated at the end of 1989. The particle size distribution was within specification. The chemical analyses indicated that the silica level was at the lower end of the specification and may have been outside the limit by 0.1 wt%. The boron level was at the upper limit of the specification. The initial qualifications of all of the presently qualified frit vendors (Cataphote, Apec, and Ferro Corp.) was described⁶. The following report describes the evaluation of the first lot of DWPF Frit 202 for Cold Runs.

EXPERIMENTAL

A sample of Cataphote DWPF Lot No. 1 was received at the Savannah River Technical Center on October 9, 1992. The sample was contained in a steel quart container inside a sealed steel one gallon container. The material was labeled as follows:

PROD.CODE SR FRIT 202
LOT 20210
DATE 10-5-92
OPER. J. PURVIS
QCTECH. R. TRIGG
TA 00 717H

The material was opened and split into eight identical samples by the QuantachromeTM rotating riffler according to Glass Technology Procedure⁷ GTOP 3-024. All subsequent samples were obtained with the riffler. Two samples were immediately removed and the moisture for these samples was determined by the GTOP 3-013 procedures. After the moisture was determined the dry material was placed in a nest of sieves and mechanically classified on a Ro-TapTM shaker for 15 minutes using the Ro-TapTM procedures and the procedures outlined in ASTM C-429 and C-92.

A random sample from the riffler was sent to Corning Engineering Laboratory Services (CELS) Corning, New York, for complete chemical analysis. Two "standard" glass samples were included for control. One control sample consisted of Frit 202 Reference Standard while a second sample was the Frit 165 Standard. Both of these materials have been thoroughly analyzed and the results described previously^{8,9}.

An additional sample was sent to the Savannah River Technology Center-Analytical Development Section for total organic and inorganic carbon determination. This test has been found to be comparable to the Chemical Oxygen Demand test⁸.

RESULTS AND DISCUSSION

Moisture and Particle Size Distribution

The moisture and measured particle size distribution for the two samples is presented in Table 2. The results from the two samples were in close agreement. The material was dry with less than the 0.1 wt% moisture. The coarse frit (greater than 80 mesh) was less than 1 wt%, as specified. The fine end of the distribution was less than 10 wt%, also as specified. The material met both the moisture and particle size specifications.

Table 2
Moisture and Particle Size Distribution - DWPF Lot 1

Cataphote	Lot 1	Lot 1	Average	
E-51768-	136-2	136-3		
Moisture	<u>Wt%</u>	<u>Wt%</u>	<u>Wt%</u>	
	0.06	0.10	0.08	
Particle Size	<u>Wt%</u>	<u>Wt%</u>	<u>Wt%</u>	Cumulative <u>Wt%</u>
+45 Mesh	0.00	0.00	0.00	0.00
+80 Mesh	0.42	0.32	0.37	0.37
+100 Mesh	5.24	5.34	5.29	5.66
+200 Mesh	86.56	86.53	86.54	92.20
-200 Mesh	7.78	7.81	7.80	100.00

Organic and Inorganic Carbon

The total organic and inorganic carbon was determined by ADS with the total carbon analyzer. Three samples were submitted with a sample of Reference Standard 202. The results are shown in Table 3. The Reference Standard was the same order of magnitude as an evaluation of this material in January of 1990. The carbon content of Lot 1 was less than 0.1 wt%.

Table 3
Total Carbon Analyses of DWPF Lot 1 and Ref. Std 202 (ppm)

Sample No.		Total Organic	Total Inorganic	Total Carbon
E-51768-136-A	Lot 1	37	18	55
-B	"	49	21	70
-C	"	48	41	89
	Avg.	45	27	72 = 0.007 wt%
E-51768-136-RS	(Ref.Std.)	433	49	482 = 0.048 wt%
Ref.Std 202	(1/12/90)			336

Chemical Analysis

The CELS laboratory performed an initial qualitative analysis of the sample and reported oxides down to 0.0001 wt%. Potassium oxide was not included in this type of analysis. The CELS laboratory then split each sample and prepared two dissolutions. Each of the glass dissolutions were analyzed on two different days by Atomic Spectroscopy. The resulting four analyses were reported along with the averages and standard deviations. The complete chemical analyses as received from CELS are included as Appendix A. Table 4 presents a summary of the results obtained from CELS and compares these values to the specification limits. Cataphote's analysis of this material is included and will be discussed in a future summary report.

Table 4
Summary of CELS Chemical Analyses of DWPF Frit 202 Lot 1

E-51768-136-DWPF-1				CELS10/92			Cataphote
Species	Specification	Range	Range	Analysis			Analysis
	Amount	Minimum	Maximum	Average*	Std.Dev.	Rel. Std	11/23/92
Majors	(Wt%)	(Wt%)	(Wt%)	(Wt%)	(Wt%)	Dev.	(Wt%)
SiO ₂	77.0±1.0	76.0	78.0	75.1	0.283	0.38%	-76.70
Na ₂ O	6.0±0.5	5.5	6.5	6.10	0.033	0.54%	5.92
Li ₂ O	7.0±0.5	6.5	7.5	6.92	0.040	0.58%	6.90
MgO	2.0±0.25	1.75	2.25	1.98	0.008	0.40%	2.01
B ₂ O ₃	8.0±0.5	7.5	8.5	8.61	0.021	0.24%	7.98
Total				98.71			99.51
Undesirable*	< 2.25		2.3	1.29			0.49
	Max (Wt%)						
ZrO ₂				ZrO ₂ (.005-.05)			0.006
Al ₂ O ₃	Al=1.0		1.89	0.35	0.008	2.29%	0.33
Fe ₂ O ₃	Fe=0.2		0.29	0.024	0.000		0.029
MnO	Mn=0.2		0.32	0.0005	0.000		0.001
NiO	Ni=0.2		0.25	0.0003	0.000		Ni=.0001
Cr ₂ O ₃	Cr=0.1		0.15	0.0004	0.000		Cr=.0001
PbO	Pb=0.1		0.11	0.0000	0.000		Pb=.0001
TiO ₂	Ti=0.15		0.25	0.0095	0.000		0.025
F	F=0.05		0.05	0.0000	0.000		<0.05
Cl	Cl=0.05		0.05	0.0000	0.000		0.013
Others >0.05				CaO(0.05-0.5)			Mo=.007
K ₂ O				MoO ₃ (.005-.05)			0.048
CaO							0.054
BaO							0.002
SO ₃							0.048
Total Oxide Wt%				99.1			100.07
				*Average of 2 dissolutions repeated 2 times (n=4)			
Moisture	< 0.1			0.08			
CCD	<0.1			0.007			
Particle Size	Wt%						
Through 80 M	≥ 99.0			99.63			
Through 200M	<10.0			7.80			
							(by differ.)

Review of this analysis including Appendix A indicated that the glass frit was well within specification on all the major oxides except SiO_2 which was 0.9 wt% below the minimum and B_2O_3 which was just slightly higher than the specification maximum by 0.11 wt%. The agreement between the four CELS measurements was excellent. The undesirable oxides were also well within the 2.25 wt% limit at 1.29 wt%. The oxide sum totaled to 99.1 wt%. The residual material may include small amounts of CaO , BaO , ZrO_2 , K_2O , SO_4 , and some H_2O .

Table 5 presents a summary of the CELS analysis for the Reference Standard Frit 202 and compares the analyzed values to the "Best Estimate" composition⁸ which was obtained after numerous analyses at various laboratories. Review of this analysis showed excellent agreement between the four measurements from CELS and the "Best Estimate" composition. The major difference was that the SiO_2 amount from this analysis was 0.2 wt% higher than "Best Estimate". The total of the oxides was 99.48, however ZrO_2 , CaO , BaO and K_2O were not determined. When these oxides are included the results agree with the "Best Estimate".

Table 5
Summary of CELS Chemical Analysis of 202 Reference Standard

E-51768-136-DWPF-1S			CELS 10/92			
Species	Specification Amount	Best Est. Oct-90	Analysis Average	Diff.	Std. Dev.	Rel Std. Dev.
Majors	(Wt%)	(Wt%)	(Wt%)	(Wt%)	(Wt%)	Dev.
SiO_2	77.0±1.0	76.6	76.8	-0.2	0.096	0.13%
Na_2O	6.0±0.5	5.9	5.82	0.08	0.043	0.74%
Li_2O	7.0±0.5	6.7	6.58	0.12	0.000	0.00%
MgO	2.0±0.25	2.0	2.00	0	0.022	1.10%
B_2O_3	8.0±0.5	7.7	7.66	0.04	0.010	0.13%
Total		98.9	98.86	0.04		
Undesirable*	< 2.25 Maximum	1.1	1.14	-0.04		
ZrO_2		0.02				
Al_2O_3	1.89	0.40	0.44	-0.04	0.013	2.95%
Fe_2O_3	0.29	0.03	0.031	-0.001	0.000	
MnO	0.26	<.01	0.0011		0.000	
NiO	0.25	<.01	0.0007		0.000	
Cr_2O_3	0.15	<.01	0.000		0.000	
PbO	0.11	0.01	0.011	-0.001	0.000	
TiO_2	0.25	0.11	0.11	0	0.000	
F	0.05	0.03	0.03	0	0.000	
Cl	0.05	0.01	0.000	0.01	0.000	
Others >0.05						
K_2O		0.19				
CaO		0.12				
BaO		0.04				
Total Oxide		99.86	99.48	0.38		
Moisture COD		<.02	0.05			

Table 6 presents a summary for the CELS chemical analysis of the Frit 165 control glass. The sample of Frit 165 was carefully analyzed in 1985. The SiO₂ was determined 10 times while the remainder of the major oxides were determined 16 times. An additional four analyses of this glass were carried out in 1989 and 1990⁸. The recent CELS analysis is in excellent agreement with all of the previous analyses. The SiO₂ value of this analysis is 0.1 wt% higher than the original 1985 analyses. The total for the oxides is identical.

Table 6
Summary of CELS Chemical Analysis of Frit 165

165 Reference Standard

E-51768-136-165S			CELS Analy.			
Species	CELS Average 3/15/85	Sigma	Average Oct-92	Diff.	Sigma	Rel. Std. Dev.
Majors	(Wt%)	(Wt%)	(Wt%)	(W%)	(Wt%)	
SiO ₂	68.89	0.075	69.0	-0.1	0.265	0.38%
Na ₂ O	12.16	0.045	11.9	0.26	0.050	0.42%
Li ₂ O	6.96	0.029	6.73	0.23	0.050	0.74%
MgO	0.99	0.010	1.03	-0.04	0.014	1.36%
B ₂ O ₃	9.32	0.064	9.35	-0.03	0.025	0.27%
Total	99.31		99.31	0.00		
Undesirable*						
ZrO ₂	0.99	0.017	1.30	-0.31	0.014	1.08%
Al ₂ O ₃			0.027		0.001	3.70%
Fe ₂ O ₃			0.085		0.000	
MnO			0.0021		0.000	
NiO			0.0091		0.000	
Cr ₂ O ₃			0.017		0.001	5.88%
PbO			0.0048		0.000	
TiO ₂			0.0022		0.000	
F						
Cl						
Others >0.05						

The overall accuracy and precision of these analyses appears to be excellent. The conclusion that the SiO₂ level for DWPF-1 was outside the specification points out the difficulty in meeting multiple interrelated specifications. This has been thoroughly discussed in previous reports^{8,9} and will not be reconsidered here. However in order to compensate for meeting the five interrelated specifications the rectangular specification limits were transformed to elliptical limits with an area increase of 25%. This should compensate for the requirement of meeting five major specifications. In addition there is a band on either side of the ellipse which describes the 95% confidence limits due to measurement variability (± 2 sigma). These ellipses are shown in Figure 1 along with the locations of DWPF-1, the 202 Reference Standard, and the "Best Estimate" value.

Figure 1. Graphical Representation of Lot 1 and Ref. Std. 202 Plotted on Elliptical Limit Plots.

It is readily apparent from this simple graphical representation that the SiO_2 level is lower than the elliptical specification limit while the Frit 202 Reference Standard is very near to the "Best Estimate values. While the B_2O_3 was slightly outside the rectangular specification, it was within the elliptical limit and was therefore acceptable.

CONCLUSIONS

1. The particle size distribution and moisture content of DWPF Frit 202 Lot 1 was within the DWPF specification.
2. The total carbon content as measured by total carbon was much less than the specified 0.1 wt%.
3. The chemical analysis of DWPF Frit 202 Lot 1 shows that the chemical composition of the frit was low in SiO_2 . All other oxides, including B_2O_3 were within the specification or within the elliptical limits.
4. The DWPF Frit 202 Lot 1 was not acceptable for DWPF Cold Runs but it was acceptable for use at TNX. The vendor was notified that the material was not acceptable.

QUALITY ASSURANCE

This work was a continuation of efforts under the Frit Qualification¹¹ and Errors of Frit¹² tasks. The procedures employed in this study were ASTM approved or as presented in the Glass Technology Procedures Manual⁷. Well documented controls were used for the chemical analyses and all data was documented¹³.

ACKNOWLEDGMENTS

The author wishes to acknowledge the efforts of Roberta Hooks for performing the physical evaluations of the frit and Carol Jantzen, who established the chemical analysis contract with CELS and was the Technical Representative.

REFERENCES

1. DWPF Waste Form Compliance Plan, Part 3, Item 500, WSRC-IM-91-116-5
2. U.S. Department of Energy, Office of Civilian Radioactive Waste Management, "Waste-Form Acceptance Preliminary Specifications for Vitrified High Level Waste Forms", June 1991.
3. WSRC-SW4-6 DWPF Waste Form Compliance Plan, Rev. 0, March 1990. (WSRC-RP-90-367. March 28, 1990).
4. "Specification for Procurement of Cold Run Frit 202, Specification No. OPS-DTE-910003", Rev.0, February 20, 1991.
5. Schumacher, R.F., "DWPF Frit Qualification-Cataphote Inc.(U)", WSRC-RP-89-1360, December 22, 1989.
6. Schumacher, R.F., "DWPF Frit Qualification-Summary", WSRC-TR-90-160, April 6, 1990.
7. "Glass Technology Procedures Manual (U)," Procedure Manual L 13-1, WSRC, Aiken SC.
8. Schumacher, R.F., "Errors of DWPF Frit Analyses-Reference Standard-II (U)", WSRC-RP-90-1219. October 22, 1990.
9. Schumacher, R.F., "Errors of DWPF Frit Analysis - Final Report-(U)" WSRC-RP-92-37, January 24, 1992.
10. Schumacher, R.F., "Acceptance of Purchased Frit by DWPF-(U)", WSRC-MS-91-507, 94th Annual Meeting Amer. Ceram. Soc. Minn., MN, April 1992.
11. Schumacher, R.F., "Research and Development Plan DWPF Frit Qualification-(U)", WSRC-RP-89-362, June 1, 1989.
12. Schumacher, R.F., "Quality Assurance/Assessment Plan Errors of DWPF Frit Analyses (U)", WSRC-RP-89-50, May 1, 1989.
13. Notebook No. E-51768, DPSTN-4648, R.F. Schumacher.

APPENDIX A

Corning Incorporated
CELS—Laboratory Services
Technology Sales & Licensing
HP ME 03 078 G6
Corning, New York 14831
800-235-2357
607-974-6601
LIX 607-974-6522

Rec 11/3/92
P. Schumacher

October 26, 1992

Dr. Carol M. Jantzen
WSRC
P.O. Box 616
Aiken, South Carolina 29808

CELS Client No.: 11988-039
Date Received : 14-OCT-92
Date Reported : 26-OCT-92
Reviewed & Approved by:

CORNING

Subcontract No. AA07192N

Copy to: CELS File

Linda P. Adams
Technical Sales Engineer

Page 1 of 5

SAMPLE IDENTIFICATION:

3 DWPF Frit Samples: DWPF 1
DWPF 1S
DWPF 165S

ANALYSIS REPORTED:

<u>Exhibit</u>	<u>Test Description</u>
A	Qualitative Chemical Analysis by QSA
B	Quantitative Chemical Analysis by Atomic Spectroscopy

COMMENTS:

Client Purchase Order No. AA07192N

Direct questions regarding this report to Linda P. Adams, CELS office.

NOTE: This report shall not be reproduced except in full, without the expressed permission of CELS - Laboratory Services.

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-039

Page 2 of 6

Exhibit A: Qualitative Chemical Analysis - QSA

Sample Description: DWPF 1

Lab I.D. No.: 23670-92

<u>Range %</u>	<u>Element Detected (Reported as Oxide)</u>
> 10	SiO ₂
5 - 20	B ₂ O ₃ , Na ₂ O
1 - 10	Li ₂ O
0.5 - 5	Al ₂ O ₃ , MgO
0.1 - 1	
0.05 - 0.5	CaO
0.01 - 0.1	Fe ₂ O ₃
0.005 - 0.05	MoO ₃ , ZrO ₂
0.001 - 0.01	MnO, TiO ₂
0.0005 - 0.005	Cr ₂ O ₃
0.0001 - 0.001	V ₂ O ₅ , CuO

Not Detected - See attached table of elements sought and their detection limits.

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-039

Page 3 of 6

Exhibit A: Qualitative Chemical Analysis - QSA

Sample Description: DWPF 1

Lab I.D. No.: 23670-92

Commentary on QSA Analysis

1. Elements sought for in general qualitative spectrographic analysis are: Cd, As, Sb, Ba, Al, B, Si, P, Mg, Mn, Pb, Sn, Ga, Cr, Fe, Ni, Bi, Ti, Be, Mo, Ca, V, Li, Cu, Ag, Na, Zn, Zr, K, Co, and Sr.
2. Elements not sought spectrographically are : C, N, O, F, He, Ne, Cl, Ar, Se, S, Br, I, Rb, Cs, Er, Hg, Nd, W.
3. Detection Limits for Qualitative Analysis:

Detection Limits (%)
(Wt. % as Common Oxide)

Ag	0.0001	Ca	0.0005	Ga	0.001	Mo	0.0005	Si	0.001
Al	0.001	Cd	0.01	Ge	0.0005	Na	0.05	Sn	0.0005
As	0.05	Ce	0.05	Hg	0.001	Ni	0.001	Sr	0.01
Au	0.001	Co	0.001	In	0.0005	P	0.1	Ti	0.0005
B	0.001	Cr	0.0005	K	1.0	Pb	0.0005	V	0.0005
Ba	0.01	Cu	0.0001	Li	0.01	Pt	0.005	Zn	0.007
Be	0.0005	Er	0.01	Mg	0.0001	Rh	0.001	Zr	0.001
Bi	0.0005	Fe	0.0007	Mn	0.0005	Sb	0.01		

4. Precision of the Qualitative Analysis is +/- 1 range % category on this exhibit.
5. Chemical species are determined as elements, but reported as common oxides per glass industry convention.
6. Oxides, e.g., the alkalis, analyzed in more sensitive spectral regions per client request will be specifically identified and respective detection limits will be indicated in the report.

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

APPENDIX A

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-039

Page 4 of 6

Exhibit B: Quantitative Chemical Analysis by Atomic Spectroscopy

Sample Description: DWPF 1

Lab I.D. No.: 23670-92

Oxides	Dis 1 Day 1	Dis 2 Day 1	Dis 1 Day 2	Dis 2 Day 2	Mean	Std. Dev.
<i>MAJOR</i>	<i>98.41</i>	<i>98.93</i>	<i>98.64</i>	<i>98.87</i>	<i>98.71</i>	<i>1.237</i>
<i>UNDESIR</i>						
Al ₂ O ₃	0.35	0.35	0.36	0.34	0.35	0.008
Al	0.19	0.19	0.19	0.18	0.19	0.005
B ₂ O ₃	8.63	8.58	8.61	8.61	8.61	0.021
B	2.68	2.66	2.67	2.67	2.67	0.008
Cr ₂ O ₃	<0.001	<0.001	<0.001	<0.001	0.000	0.000
Cr	<0.0007	<0.0007	<0.0007	<0.0007	0.000	0.000
Fe ₂ O ₃	0.024	0.024	0.024	0.024	0.024	0.000
Fe	0.017	0.017	0.017	0.017	0.017	0.000
Li ₂ O	6.98	6.92	6.89	6.90	6.92	0.040
Li	3.24	3.21	3.20	3.21	3.22	0.017
MgO	1.98	1.99	1.97	1.98	1.98	0.008
Mg	1.19	1.20	1.19	1.19	1.19	0.005
MnO	0.0005	0.0005	0.0005	0.0005	0.0005	0.000
Mn	0.0004	0.0004	0.0004	0.0004	0.0004	0.000
Na ₂ O	6.12	6.14	6.07	6.08	6.10	0.033
Na	4.54	4.56	4.50	4.51	4.53	0.028
NiO	0.0004	0.0005	0.0004	0.0004	0.0004	0.000
Ni	0.0003	0.0004	0.0003	0.0003	0.0003	0.000
PbO	<0.001	<0.001	<0.001	<0.001	0.0000	0.000
Pb	<0.0009	<0.0009	<0.0009	<0.0009	0.0000	0.000
SiO ₂	74.7	75.3	75.1	75.3	75.1	0.283
Si	34.9	35.2	35.1	35.2	35.1	0.141
TiO ₂	0.0098	0.0092	0.0098	0.0092	0.0095	0.000
Ti	0.0059	0.0055	0.0059	0.0055	0.0057	0.000
F-	<0.01	<0.01	<0.01	<0.01	0.0000	0.000
Cl-	<0.02	<0.02	<0.02	<0.02	0.0000	0.000
<i>Total</i>	<i>98.78</i>	<i>99.31</i>	<i>99.03</i>	<i>99.24</i>	<i>99.10</i>	<i>0.238</i>
Oxide Total						0

Dis 1 and Dis 2 - Dissolution 1 and 2
Day 1 and Day 2 - 1st and 2nd Analysis (read)

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

APPENDIX A

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-039

Page 5 of 6

Exhibit B: Quantitative Chemical Analysis by Atomic Spectroscopy

Sample Description: DWPF 1S

Lab I.D. No.: 23670-92

Oxides	Dis 1 Day 1	Dis 2 Day 1	Dis 1 Day 2	Dis 2 Day 2	Mean	Std. Dev.
<i>MAJ.</i>	<i>98.89</i>	<i>98.80</i>	<i>98.75</i>	<i>98.90</i>	<i>98.83</i>	<i>.072</i>
Al ₂ O ₃	0.46	0.44	0.44	0.43	0.44	0.013
Al	0.24	0.23	0.23	0.23	0.23	0.005
B ₂ O ₃	7.67	7.65	7.65	7.65	7.66	0.010
B	2.38	2.38	2.38	2.38	2.38	0.000
Cr ₂ O ₃	<0.001	<0.001	<0.001	<0.001	0.000	0.000
Cr	<0.0007	<0.0007	<0.0007	<0.0007	0.000	0.000
Fe ₂ O ₃	0.031	0.031	0.031	0.031	0.031	0.000
Fe	0.022	0.022	0.022	0.022	0.022	0.000
Li ₂ O	6.58	6.58	6.58	6.58	6.58	0.000
Li	3.06	3.06	3.06	3.06	3.06	0.000
MgO	1.98	2.01	1.99	2.03	2.00	0.022
Mg	1.19	1.21	1.20	1.22	1.21	0.013
MnO	0.0011	0.0011	0.0011	0.0011	0.0011	0.000
Mn	0.0009	0.0009	0.0009	0.0009	0.0009	0.000
Na ₂ O	5.76	5.86	5.83	5.84	5.82	0.043
Na	4.27	4.35	4.33	4.33	4.32	0.035
NiO	0.0008	0.0006	0.0006	0.0006	0.0007	0.000
Ni	0.0006	0.0005	0.0005	0.0005	0.0005	0.000
PbO	0.011	0.012	0.011	0.011	0.011	0.001
Pb	0.010	0.011	0.010	0.010	0.010	0.000
SiO ₂	76.9	76.7	76.7	76.8	76.8	0.096
Si	36.0	35.9	35.9	35.9	35.9	0.050
TiO ₂	0.11	0.11	0.11	0.11	0.11	0.000
Ti	0.066	0.066	0.066	0.066	0.066	0.000
F-	0.03	0.03	0.03	0.03	0.030	0.000
Cl-	<0.02	<0.02	<0.02	<0.02	0.000	0.000
<i>Total</i>	<i>99.50</i>	<i>99.39</i>	<i>99.34</i>	<i>99.48</i>	<i>99.43</i>	<i>.075</i>
Oxide Total					99.46	

Dis 1 and Dis 2 - Dissolution 1 and 2
Day 1 and Day 2 - 1st and 2nd Analysis (read)

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

APPENDIX A.

LABORATORY ANALYSIS REPORT

CELS Client No.: 11988-039

Page 6 of 6

Exhibit B: Quantitative Chemical Analysis by Atomic Spectroscopy

Sample Description: DWPF 165S

Lab I.D. No.: 23670-92

Oxides	Dis 1 Day 1	Dis 2 Day 1	Dis 1 Day 2	Dis 2 Day 2	Mean	Std. Dev.
Al ₂ O ₃	0.026	0.026	0.028	0.026	0.027	0.001
Al	0.014	0.014	0.015	0.014	0.014	0.000
B ₂ O ₃	9.35	9.34	9.38	9.32	9.35	0.025
B	2.90	2.90	2.91	2.89	2.90	0.008
Cr ₂ O ₃	0.016	0.017	0.017	0.018	0.017	0.001
Cr	0.011	0.012	0.012	0.012	0.012	0.000
Fe ₂ O ₃	0.087	0.083	0.088	0.083	0.085	0.000
Fe	0.061	0.058	0.062	0.061	0.061	0.000
Li ₂ O	6.69	6.78	6.76	6.68	6.73	0.050
Li	3.11	3.15	3.14	3.10	3.13	0.024
MgO	1.01	1.04	1.03	1.04	1.03	0.014
Mg	0.61	0.63	0.62	0.63	0.62	0.010
MnO	0.0021	0.0020	0.0022	0.0020	0.0021	0.000
Mn	0.0016	0.0015	0.0017	0.0015	0.0016	0.000
Na ₂ O	11.9	12.0	11.9	11.9	11.9	0.050
Na	8.83	8.90	8.83	8.83	8.85	0.035
NiO	0.0092	0.0089	0.0093	0.0089	0.0091	0.000
Ni	0.0072	0.0070	0.0073	0.0070	0.0071	0.000
PbO	0.0044	0.0048	0.0051	0.0049	0.0048	0.000
Pb	0.0041	0.0045	0.0047	0.0045	0.0045	0.000
SiO ₂	69.0	68.8	69.3	68.7	69.0	0.265
Si	32.3	32.2	32.4	32.1	32.3	0.129
TiO ₂	0.0023	0.0021	0.0024	0.0020	0.0022	0.000
Ti	0.0014	0.0013	0.0014	0.0012	0.0013	0.000
ZrO ₂	1.28	1.31	1.31	1.30	1.30	0.014
Zr	0.95	0.97	0.97	0.96	0.96	

Total Oxide 99.43

Dis 1 and Dis 2 - Dissolution 1 and 2

Day 1 and Day 2 - 1st and 2nd Analysis (read)

CONFIDENTIAL:

This CELS report information is to be used only for account 11988.

END

DATE
FILMED

7 / 1 / 93