DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

STEAM GASIFICATION OF CARBON: CATALYST PROPERTIES

Final Report: September 15, 1988 - October 31, 1992

Prepared for U.S. D.O.E. Grant Number: DE-FG22-88PC 88915

University of Colorado Proposal Number: 0188.11.0115B

Project officer: Kamalendu Das

Principal Investigator:

Professor John L. Falconer

January 10, 1993

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DOE/PC/88915--T17

JAN 14

DE93 011515

APR 15 1993

CSTI

Table of Contents

	Page
Abstract	3
Introduction	3
Objectives and Scope of Research	4
Research Plan	4
Project Status, Accomplishments, and Technical Discussion	6
Conclusions	7
Appendices	8
Research Workers	8
Thesis Abstracts	9
Publications and Presentations	10

ABSTRACT

This research uses several techniques to measure the concentration of catalyst sites and determine their stoichiometry for the catalyzed gasification of carbon. Both alkali and alkaline earth oxides are effective catalysts for accelerating the gasification rate of coal chars, but only a fraction of the catalyst appears to be in a form that is effective for gasification, and the composition of that catalyst is not established. Transient techniques, with ^{13}C labeling, are being used to study the surface processes, to measure the concentration of active sites, and to determine the specific reaction rates.

We have used secondary ion mass spectrometry (SIMS) for both high surface area samples of carbon/alkali carbonate mixtures and for model carbon surfaces with deposited alkali atoms. SIMS provides a direct measure of surface composition. The combination of these results can provide knowledge of catalyst dispersion and composition, and thus indicate the way to optimally utilize carbon gasification catalysts.

INTRODUCTION

Coal gasification by steam is of critical importance in converting coal to gaseous products (CO , H_2 , CO_2 , CH_4) that can then be further converted to synthetic natural gas and higher hydrocarbon fuels. Alkali and alkaline earth metals (present as oxides) catalyze coal gasification reactions and cause them to occur at significantly lower temperatures. A more fundamental understanding of the mechanism of the steam gasification reaction and catalyst utilization may well lead to better production techniques, increased gasification rates, greater yields, and less waste.

We are studying the gasification of carbon by steam in the presence of alkali and alkaline earth oxides, using carbonates as the starting materials. Carbon dioxide gasification ($\text{CO}_2 + \text{C} \rightarrow 2\text{CO}$) has been studied in some detail recently, but much less has been done on the actual steam gasification reaction, which is the main thrust of our work. In particular, the form of the active catalyst compound during reaction is still questioned and the dependence of the concentration of active sites on reaction parameters is not known. Until recently, no measurements of active site concentrations during reaction had been made. We have recently used transient isotope tracing to determine active site concentration during CO_2 gasification.

We are investigating the mechanism and the concentration of active sites for steam gasification with transient isotopic tracing. For this technique, the reactant feed is switched from H_2O to isotopically-labeled water at the same concentration and flow rate. We can then directly measure, at reaction conditions, the concentration of active catalytic sites, their kinetic rate constants, and the presence of more than one rate constant. This procedure allows us to obtain transient kinetic data without perturbing the steady-state surface reaction. A mass spectrometer with computer interface allows each of the appropriate mass peaks to be followed in time. The changes in catalytic site concentrations and their rate constants will be measured as a function of reaction time, initial catalyst concentration, and reaction temperature. Potassium and calcium salts are being used.

The composition of the active catalyst is being studied with secondary ion mass spectrometry.

try (SIMS) for catalyst-carbon mixtures, after high temperature treatment in steam. Model catalyst-carbon surfaces are being prepared so that a planar surface can be obtained for SIMS analysis. Details of the local bonding in reacting solids can also be obtained with SIMS. Scanning tunneling microscopy (STM), a new technique that can obtain atomic images of surfaces with excellent resolution, is being used to determine the location and distribution of catalysts on carbon surfaces. This will be a direct measure of catalyst location and size. By combining SIMS, STM, and transient isotope tracing, we will obtain a detailed understanding of the utilization of the catalyst, its location on the surface, and its chemical form. This information will help in improving catalyst utilization in steam gasification of coal.

OBJECTIVES AND SCOPE OF RESEARCH

The objectives of this research are to determine the catalyst composition and concentration for metal oxide (potassium and calcium oxides) catalyzed gasification of carbon. The scope of this research involves determining:

- The concentration of active catalytic sites (and thus the dispersion), at reaction conditions, as a function of temperature, carbon burnoff, catalyst loading, and catalyst type.
- The location of catalyst, on the surface, on an atomic scale.
- The composition of the catalyst.
- The site-specific rate constant for steam gasification.
- Insight into the reaction mechanism.
- How to maximize catalyst dispersion.

Knowledge of how catalyst dispersion depends on reaction conditions will provide a basis for making optimal use of the catalyst in steam gasification of coal.

RESEARCH PLAN

The catalyst composition, concentration, and location for catalyzed gasification of carbon and coal char by steam will be investigated for both alkali metal and alkaline earth carbonates. Isotope tracing will measure the concentration of active catalyst sites, their specific rate constant, and the dependence of sites on initial catalyst loading, carbon conversion (burnoff), and temperature. Transient isotope tracing, secondary ion mass spectrometry (SIMS), and scanning tunneling microscopy (STM), will be used to obtain a complete picture of the catalysts at reaction conditions.

Carbon black, coal chars, and graphite will be used in the transient tracing experiments. In the SIMS and STM experiments, graphite and carbon deposited on a metal surface will be models of coal char. These forms will allow better utilization of these sensitive surface techniques.

Isotope Tracing Experiments: Transient isotope tracing allows the rate constant and the effective active site concentration to be uncoupled so that a direct measure of reactive site concentration can be obtained. The presence of more than one type of site can also be determined. Isotope tracing can also identify the rate-determining step. We are applying isotope tracing to catalyzed gasification of carbon by steam. A small amount of carbon, impregnated with K_2CO_3 , will be

heated to reaction conditions in a $\text{H}_2\text{O}/\text{He}$ steam. The H_2 , CO , and CO_2 reaction products and unreacted H_2O will be detected with a quadrupole mass spectrometer located immediately downstream from the reactor. Transient mass signals will be measured as H_2^{18}O replaces H_2^{16}O in the feed stream (step increase in H_2^{18}O and step decrease in H_2^{16}O). A computer interfaced to the mass spectrometer allows C^{18}O , C^{16}O , C^{16}O_2 , C^{18}O_2 , $\text{C}^{16}\text{O}^{18}\text{O}$, H_2^{16}O , H_2^{18}O and H_2 products to be detected simultaneously as a function of time. As soon as the ^{18}O products reach steady state, the H_2^{18}O will be replaced by H_2^{16}O to repeat the process.

Since the partial pressure of steam is unchanged when the isotopes are switched, steady-state reaction is not disturbed, but the isotopic composition of the product mix must adapt itself to the isotopic composition of the feed. A kinetic isotope effect may change the steady-state reaction site, however. This relaxation provides mechanistic information.

These transient isotope experiments will be carried out for a range of reaction conditions to determine what fraction of the catalyst is active for reaction:

- Initial catalyst weight loading will be varied to determine how active site concentration varies with catalyst concentration. The catalyst/carbon ratio will vary with carbon conversion, and thus the concentration of active sites will also be measured as a function of burnoff.
- Reaction temperature will be varied to determine how the number of active sites varies with temperature. At higher temperatures, the loss of K metal can be checked by re-measuring active site concentrations at lower temperatures.
- Both K and Ca catalysts will be used. A better understanding of the role of the catalyst can be obtained by determining the differences between alkali and alkaline earth catalysts.

Secondary Ion Mass Spectrometry (SIMS): Secondary ion mass spectrometry consists of bombarding a surface under UHV conditions with energetic primary ions (typically Ar^+) at sufficient atomic motion to eject particles from the surface. Some of the ejected particles are ionic (secondary ions) and are mass analyzed by a mass spectrometer to give the secondary ion mass spectrum. To prevent significant impact damage to the surface, the experiment is normally conducted in the static mode using a low primary ion current density (typically $1\text{--}10 \times 10^{-9} \text{ A/cm}^2$).

SIMS will be used to probe the identity and reaction chemistry of the species present during catalytic steam gasification. SIMS has unique potential for this since molecular species can be ejected from the surface with their original structure preserved and can therefore be identified directly from the SIMS spectrum.

SIMS will also be used to probe the local chemical environment of surface components. Ejected molecular cluster ions form by reassociation of independently-ejected surface components that are within close proximity of each other (typically 1-5 Å). These molecular clusters are thus indicative of a close proximity between the cluster components on the original surface. This information is essential for a complete understanding of the surface reaction chemistry. SIMS can selectively probe the local environment of such components through the formation of cluster ions containing these components. These capabilities of SIMS for probing the identity, reaction chemistry, and local chemical environment of surface species will be exploited to develop a better understanding of catalytic gasification chemistry.

Carbonate-carbon samples will be examined by SIMS before and after exposure to reaction conditions to identify the chemical species present on the active surface and their local chemical environment. The effects of reaction temperature, burnoff time, and catalyst loading will be studied for both potassium and calcium catalysts.

Model carbon surfaces will be prepared to produce a cleaner and more well defined carbon surface than that of the carbon black samples, which contain hydrocarbon and oxygenated impurities. Since our previous work shows that the metal-carbonate catalysts thermally decompose to oxides, we will attempt to place the active catalyst on the carbon surface by first vapor depositing, in UHV, the alkali metal and then forming the alkali metal oxide by exposure to oxygen. The nature of the interaction of water with both calcium and potassium oxides on such model surfaces will be determined by SIMS analysis before and during exposure to a H_2O beam in UHV. The effects of temperature, metal oxide coverage, H_2O pressure, and exposure time to the H_2O beam will be studied.

Scanning Tunneling Microscopy (STM): Since the dispersion of the catalyst can significantly affect the reaction rate, we will measure catalyst particle size to determine how dispersion depends on catalyst concentration, surface structure, and temperature. We will also determine the atomic location of the catalyst on the surface. By using graphite with few grain boundaries and thin layers of carbon deposited onto a single crystal metal, we will study the influence of surface structure.

Scanning tunneling microscopy (STM) is nondestructive and yields real-space imaging on an atomic dimension. Experimentally, electric current flows between an atomically sharp needle and the surface of interest. The extreme sensitivity of the tunneling current to tunneling distance is the basis of operation. Tunneling current decreases by roughly ten times for each increase of 0.1 nm spacing. If the needle is scanned laterally across the surface of interest, while the distance between needle and surface is adjusted to maintain a constant tunnel current, the topography of the surface can be obtained. Lateral resolution of 0.1 nm and height corrugations of 0.01 nm have been obtained. The unique advantages of STM are its atomic resolution (individual atoms can be detected) and its direct measure of surface atom location and structure.

PROJECT ACCOMPLISHMENTS AND TECHNICAL DISCUSSION

Research on this grant was concentrated in three areas: secondary ion mass spectrometry, transient isotope tracing, and scanning tunneling microscopy, and the results will be discussed in that order.

Secondary Ion Mass Spectroscopy (SIMS) Studies

Model carbon surfaces were deposited on Ta to carry out SIMS studies of catalyst/carbon system. Both Auger electron spectroscopy (AES) and SIMS were used in ultrahigh vacuum to characterize the surfaces. Auger spectroscopy showed that the carbon surfaces were clean and free of oxygen. A Getter source was used to deposit potassium onto the carbon surface. The carbon surface was first cleaned by high temperature treatments, which were obtained by electron bombardment heating. Both positive and negative SIMS were used following potassium

adsorption at 300 K, following treating of potassium layers on graphite, O_2 adsorption at 300 K on the potassium layers, and during heating of CO-adsorbed potassium and oxygen layers on graphite.

During potassium adsorption at 300 K, much of the adsorbed potassium is incorporated into the sub-surface of the carbon. Heating further decreases the potassium surface coverage. Adsorption of oxygen increased the potassium surface coverage but stable oxides did not form according to the SIMS results. At high temperatures (800 K) K_2O does form and it decomposes at higher temperatures. The formation of K_2O is at the same temperatures as K_2CO_3 decomposed in other studies. Details of these results are in the attached publication.

Transient Isotope Tracing

Major modifications were made in the transient isotope tracing system to reduce the delay time which also caused a spread in the step function signal change. The following transient studies were carried out:

- 1) A carbon sample containing reduced catalyst was exposed at high temperature to a step increase in CO_2 flow. The CO signal significantly overshoot the steady state gasification value. This overshoot allowed the concentration of oxidizable sites to be measured.
- 2) A ^{13}C sample containing a potassium catalyst was run at steady state reaction in flowing $^{13}CO_2$. The $^{13}CO_2$ flow was replaced in a step function, with helium flow and the responses of the ^{12}CO and ^{13}CO signals were followed.

These experiments were complicated because the CO_2 signal is much larger than the CO product signal and thus the cracking fraction of CO_2 at mass 28 caused a large correction to the CO signal. Also, isotope exchange, which is an inherent step in the reaction, creates $^{13}CO_2$ whenever ^{13}CO is formed and the exchange is fast relative to ^{13}CO formation. Thus, the actual formation rate of ^{13}CO from the decomposition step on the surface must take the rate of $^{13}CO_2$ formation into account. Concentrations of active sites were measured for a series of catalyst/carbon mixtures.

Temperature-programmed reaction experiments were completed on iron catalyzed gasification of carbon by carbon dioxide. This system exhibits interesting activity patterns. The number of active sites appears to depend significantly on temperature.

Details of the transient experiments are in the attached thesis abstracts. These theses have already been submitted to DOE.

Scanning Tunneling Microscopy

The STM System was modified a number of times and the electronics and the hardware were separately returned to the manufacturers for modifications. In spite of extensive efforts we have not been able to obtain atomic resolution on this system.

CONCLUSIONS

Secondary ion mass spectrometry is an effective means to study catalyst intermediates in the gasification reaction. Potassium, deposited onto a graphite surface at 310 K, readily diffuses into the graphite bulk to form intercalation compounds. At elevated temperatures the intercala-

tion compounds decompose, and potassium diffuses to the surface to desorb. The combination of AES and SIMS analysis indicates that the potassium surface concentrations are low at all conditions. Exposure to O_2 at 310 K readily segregates potassium to the surface, but no indication was obtained of K_2O formation at these conditions. As the temperature was raised above 700 K, molecular K_2O species formed, and above 950 K, the molecular K_2O species decomposes. The use of SIMS allows a direct observation of the presence of molecular K_2O .

Transient isotope tracing is difficult to apply to CO_2 gasification of carbon at steady state conditions because of the cracking of CO_2 to CO in the mass spectrometer and because of the inherent exchange processes that are fast relative to gasification. These exchange processes significantly complicated the analysis of mass spectrometer signals.

Transient isotope tracing, which is isotope substitution at steady-state, was concluded to be ineffective for carbon gasification because of the exchange reactions that take place. Instead, two types of transient experiments were used to study the reaction between $^{12}CO_2(g)$ and K_2CO_3 -catalyzed $^{13}C(s)$. The experiments were characterized by a rapid change in feed composition flowing over $K_2CO_3/^{13}C$ samples containing 4, 6, and 10% K_2CO_3 by weight. The $K_2CO_3/^{13}C$ sample was decomposed in He, the temperature was lowered, and the feed was switched from He to $^{12}CO_2/He/Ar$. The old feed stream was replaced by the new feed stream in 2.7 s. The product response to the sudden $^{12}CO_2(g)$ exposure was consistent with the oxidation-reduction mechanism. Carbon monoxide formed from gas phase CO_2 and from solid carbon and catalyst oxygen. The rate of oxygen accumulation by the sample was integrated over time and a steady-state potassium to oxygen ratio was obtained. Carbon samples containing 4, 6, and 10% K_2CO_3 have K:O ratios of one during steady state reaction at the temperatures studied. These experiments also indicated that some chemisorbed CO_2 is present on the surface during gasification.

The feed was switched to He after the sample attained steady-state reaction in $^{12}CO_2/He/Ar$, and the production rate of ^{13}C -containing products rapidly declined and then underwent an exponential decay in time. The rate constant of the elementary step that converts solid carbon into carbon monoxide was found from the time constant of the exponential decay in ^{13}C -containing products. The activation energy and preexponential factor were determined for the rate constant of the 4 and 10 wt% samples. The total active site concentration of the elementary step was determined from the rate constant, the steady-state reaction rate, and equilibrium constant, and the effluent ratio of $CO(g)$ to $CO_2(g)$.

RESEARCH WORKERS

Todd Bell, undergraduate student

Alex Rosen, MS student

David Perkins, MS student

Joshua Chang, PhD student

Prof. Keith Kester, Visiting Professor

Prof. Lee L. Lauderback, co-PI

Prof. John L. Falconer, co-PI

THESIS ABSTRACTS

Perkins, David Allen (M.S., Chemical Engineering)

Transient Isotope Studies of Iron-Catalyzed Gasification of Carbon

Thesis directed by Professor John L. Falconer

Temperature-programmed (reaction (TPR), transient isotope tracing, isotope labeling, and mass spectrometry were employed to study CO_2 gasification of carbon in the presence of an iron catalyst. Transient isotope tracing and mass spectrometry were further used to determine the amounts of active catalyst sites in potassium carbonate-catalyzed carbon gasification and CO_2 methanation over a Ni/SiO_2 catalyst.

Temperature-programmed reaction experiments provided information regarding catalyst activity and reaction mechanism. TPR studies of $\text{Fe}/^{13}\text{C}$ indicated that iron is a highly active catalyst for carbon gasification when present in the elemental form. Gasification commenced below 800 K for samples in which the catalyst was in a reduced form. Iron-catalyzed gasification was autocatalytic for some $\text{Fe}/^{13}\text{C}$ samples; product CO reduced the iron. This activated the catalyst and caused a greater production rate of CO. The number of active sites, obtained from transient isotope tracing experiments, increased with increasing temperature but was independent of iron concentration in the 580 ppm to 1.8 wt% Fe range. A mechanism was proposed to describe iron-catalyzed carbon gasification in which the CO_2 was transferred to the carbon prior to reaction.

The population of active sites for potassium-catalyzed carbon gasification was determined from transient isotope tracing results as a function of catalyst loading, temperature, and time-on-stream. The number of active sites increased with increasing temperature and decreased with time-on-stream. The number of active sites was larger for 10% than for 5% K_2CO_3 loading only at the higher temperatures studied.

The effect of temperature on active sites for CO_2 methanation over Ni/SiO_2 catalyst was studied using transient isotope tracing. The fraction of sites active for methanation increased by a factor of 3.4 from 470 to 570 K. An activation energy for active site formation of 15 kJ/mol was calculated. The fraction of sites that were active for CO_2 hydrogenation was similar to that reported in a similar study of CO hydrogenation.

Rosen, Alexander Paul

Transient Studies of Potassium-Carbonate-Catalyzed Carbon Gasification

Thesis directed by Professor John L. Falconer

Two types of transient experiments were used to study the reaction between $^{12}\text{CO}_2(\text{g})$ and K_2CO_3 -catalyzed $^{13}\text{C}(\text{s})$. The experiments were characterized by a rapid change in feed composition flowing over $\text{K}_2\text{CO}_3/^{13}\text{C}$ samples containing 4, 6, and 10% K_2CO_3 by weight. The $\text{K}_2\text{CO}_3/^{13}\text{C}$ sample was decomposed in He, the temperature was lowered, and the feed was switched from He to $^{12}\text{CO}_2/\text{He}/\text{Ar}$. The old feed stream was replaced by the new feed stream in 2.7 s. The product response to the sudden $^{12}\text{CO}_2(\text{g})$ exposure was consistent with the oxidation-reduction mechanism. Carbon monoxide formed from gas phase CO_2 and from solid carbon and catalyst oxygen. The rate of oxygen accumulation by the sample was integrated over time and a steady-state potassium to oxygen ratio was obtained.

The feed was switched to He after the sample attained steady-state reaction in $^{12}\text{CO}_2/\text{He}/\text{Ar}$, and the production rate of ^{13}C -containing products rapidly declined and then underwent an exponential decay in time. The rate constant of the elementary step that converts solid carbon into carbon monoxide was found from the time constant of the exponential decay in ^{13}C -containing products. The activation energy and preexponential factor were determined for the rate constant of the 4 and 10 wt% samples. The total active site concentration of the elementary step was determined from the rate constant. The steady-state reaction rate, and equilibrium constant, and the effluent ratio of $\text{CO}(\text{g})$ to $\text{CO}_2(\text{g})$.

PUBLICATIONS AND PRESENTATIONS

Chang, J.S., Lauderback, L.L., and Falconer, J.L., "AES and SIMS Analysis of Potassium/Graphite Surfaces," *Carbon*, **29**, 645-652 (1991).

"A SIMS Study of the Interaction of Potassium Carbonate with Carbon Black," presented at the 19th Biannual Conference on Carbon, Pennsylvania State University, State College, Pennsylvania, June 25-30, 1989.

"Steam Gasification of Carbon: Catalyst Properties" presented at the University Coal Research Contractors Review Meeting, July 1990 and June 1991.

"Steam Gasification of Carbon: Catalyst Properties" presented at DOE Review of Fossil Energy Advanced Research Projects, October 24, 1990.

END

**DATE
FILMED**

5 / 10 / 93