D. B. Moore
D. B. Moore, Section Manager
Authorized Derivative Classifier

HEAVY METAL REMOVAL AND RECOVERY USING MICROORGANISMS (U)

VOLUME I

STATE-OF-THE-ART AND POTENTIAL APPLICATIONS AT THE SRS

by

Edward W. Wilde

Westinghouse Savannah River Company
Savannah River Site
Aiken, SC 29808

and

John R. Benemann

Consultant
1212 Kelly Court
Pinole, CA 94564

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Approved by: D. B. Moore

Date 3/26/91

M8909021

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

FOREWORD

This report describes the results of a comprehensive review of the literature on the subject of bioremoval for the reduction and reclamation of heavy metals from wastewaters. Volume I summarizes the findings of specific relevance to SRS and proposes a course of action. Volume II provides a detailed discussion of the findings from the literature review.

77

ABSTRACT

Microorganisms - bacteria, fungi, and microalgae - can accumulate relatively large amounts of toxic heavy metals and radionuclides from the environment. These organisms often exhibit specificity for particular metals. The metal content of microbial biomass can be a substantial fraction of total dry weight with concentration factors (metal in dry biomass to metal in solution) exceeding one million in some cases. Both living and inert (dead) microbial biomass can be used to reduce heavy metal concentrations in contaminated waters to very low levels - parts per billion and even lower. Commercial applications of this potentially powerful new technology which we term "bioremoval" have been recently introduced, specifically in the removal of metals from the electronics industry wastewaters and gold mining operations.

In many respects (e.g. specificity, residual metal concentrations, accumulation factors, and economics) microbial bioremoval processes can be superior to conventional processes, such as ion exchange and caustic (lime or hydroxide) precipitation for heavy metals removal from waste and contaminated waters. Thus, bioremoval could be developed to contribute to the clean-up of wastes at the Savannah River Site (SRS) and other DOE facilities. However, the potential advantages of bioremoval processes must still be developed into practical operating systems. A detailed review of the literature suggests that appropriate bioremoval processes could be developed for the SRS.

There is great variability from one biomass source to another in bioremoval capabilities. Bioremoval is affected by pH, other ions, temperature, and many other factors. The biological (living vs. dead) and physical (immobilized vs. dispersed) characteristics of the biomass also greatly affect metal binding. Even subtle differences in the microbial biomass, such as the conditions under which it was cultivated, can have major effects on heavy metal binding. Because of the large number of variables, the optimal biomass sources and conditions for bioremoval must be established for each metal and specific application.

The large number of possible biomass sources requires a priori selection of the most likely candidates for such a screening and R&D effort. The commercial success of bioremoval processes based on microalgae biomass, the extensive literature on microalgae bioremoval, and the fact that an algaculture research project is presently being conducted at the SRS, suggest that a bioremoval project at SRS should concentrate on these microorganisms. An exploratory R&D project is described.

TABLE OF CONTENTS

Foreword	i
Abstract	ii
Table of Contents	iii
1.0 INTRODUCTION	1
2.0 FINDINGS FROM THE LITERATURE REVIEW	3
2.1 Introduction	3
2.2 Comparison of Bioremoval with Conventional Technologies	4
2.3 Mechanisms of Bioremoval	8
2.4 Selection of the Microbial Biomass	10
2.5 Rationale for Selection of Microalgae	12
2.6 State-of-the-Art of Microalgae Bioremoval	13
2.7 Bioremoval Process Development	16
3.0 POTENTIAL APPLICATIONS OF BIOREMOVAL AT THE SRS	18
4.0 RESEARCH PLAN	20
5.0 CONCLUSIONS	21
6.0 LITERATURE CITED	22

1.0 INTRODUCTION

Heavy metals and radionuclides, waste materials produced during weapons material production at SRS and other DOE facilities, constitute a substantial national environmental problem (DOE, 1989). New technologies must be developed to deal in a cost-effective manner with both current and past waste management and remediation problems. A major factor in the toxic and hazardous nature of such wastes is the bioconcentration of heavy metals and radionuclides by living organisms. As these elements are incorporated into the food chain they are often preferentially retained and further concentrated.

Human beings, at the apex of the food chain, are among the most, though not the only, affected. In one classic case, reviewed by Polikarpov (1966), an unexplained increase in ^{65}Zn in an individual working at the Hanford facility was traced to oysters bought on the Pacific Coast, 250 miles away. The radionuclide was discharged into the Columbia river from Hanford, accumulated by marine microalgae in the estuary and bioconcentrated into the microalgae consuming oysters, by a factor of 200,000 fold above the surrounding seawater.

It is generally desirable to separate and remove heavy metals and radionuclides before they are diluted and mixed with other wastes. However, in many situations this is not practical and waste treatment processes must deal with relatively dilute, though still potentially hazardous or undesirable, heavy metal containing wastes. Also, many situations exist where past contamination of ground or surface waters or soils resulted in a wide distribution of the hazardous wastes that contain relatively low heavy metal concentrations. Processes are required to remediate these wastewaters and to reclaim the trace amounts of heavy metals in them.

A number of commercial processes for heavy metal removal are currently used: ion exchange, chemical precipitation, reverse osmosis, solvent extraction, and activated carbon adsorption. Often, these processes are not adequate for particular situations: removal efficiencies are not high enough, they can not deal with low concentrations of metals, selectivity is poor, and there is interference by other metals, ions, and contaminants. Novel methods are required for the cost-effective treatment of heavy metal wastes currently being generated and for the remediation of contaminated environments.

The natural bioaccumulation processes of living organisms, which lead to the transfer of heavy metals from the environment into microbial biomass, can be adapted to the requirements of heavy metals removal from waste and contaminated waters - potentially making the problem part of the solution. Either living microorganisms, or inert (dried or heat-killed) microbial biomass can be used in such "bioremoval" processes. Bioremoval encompasses adsorption of metal ions to the surface of microbial cells and absorption of metals into the cells. A number of different mechanisms are involved in each of these processes.

Microbial bioremoval processes have potential advantages over conventional methods in terms of specificity of metals removed, lack of interference by other ions, the ability to remove metals when they occur at very low concentrations, and overall economics. Although some commercial applications have been achieved, the full advantages of bioremoval processes have not yet been exploited.

During the development of a proposed algaculture project at the SRS involving L Lake (Wilde and Benemann, 1989), a preliminary literature search for potential applications of the microalgae biomass that would be derived from such a process revealed a considerable body of literature on the uptake of heavy metals by microalgae. Considering the waste treatment and clean-up problems faced by the SRS, and the DOE weapons facilities in general, a comprehensive literature review effort was initiated to review the state-of-the-art of microbial bioremoval and identify potential areas in which this technology could be applied to specific problems at the SRS and, if warranted, suggest a preliminary research and development (R&D) plan.

An extensive and rapidly growing literature deals with the basic phenomenon of microbial bioremoval and the potential applications of such processes. Recent reviews include those of Gadd, (1989), Olson et al., (1989), Macaskie and Dean, (1989), and Volesky (1990). A brief overview of the conclusions from this state-of-the-art review are presented in the next section of this volume. For more details and literature citations, Volume II should be consulted. Based on this review, and considerations of several potential applications of this technology at the SRS (Section 3), as well as specific capabilities at the SRS, a two-stage R&D Plan was formulated (Section 4). The technology developed under this project would have applications at other DOE facilities and, indeed, in environmental protection generally.

Microorganisms can concentrate minute concentrations (ppb range or even lower) of metals from the environment under a variety of conditions and with high specificity. Based on the existing literature and experience, the development of practical processes can be projected with confidence. The rapidly developing technology of bioaccumulation could potentially reduce the cost of environmental clean-up at SRS and similar sites by a large factor.

2.0 FINDINGS FROM THE LITERATURE REVIEW

2.1 Introduction

Although some heavy metals, such as Mo, Zn, Cu, etc., are required in minute quantities by living organisms, including man, others, such as Pb, Cd, and Hg, have no known biological function and are generally toxic, at concentrations as low as parts per billion (ppb) in the environment. Even the essential heavy metals can be toxic at concentrations above those which are required for biological function. Radionuclides, which are often isotopes of heavy metals, can be toxic because of their bioaccumulation by living organisms and damage to nucleic acids and other essential biological molecules caused by ionizing radiation.

Heavy metal toxicity is due to the attachment of the metal ions to various biological macromolecules, in particular proteins. Many proteins contain -SH (thiol) groups, similar in reactivity to H₂S. Like hydrogen sulfide, protein -SH groups have a high affinity for heavy metals, and heavy metal toxicity roughly correlates with the solubility product of the metal sulfides. Some proteins have particularly reactive -SH groups, which are typically involved in the catalytic (enzyme) activity of the protein. Many proteins bind specific essential heavy metals to such -SH groups, which are crucial to the activity of the enzymes. Toxic metals also bind to such sites, resulting in the loss of enzyme activity, a decline in metabolic activity, and, if a sufficient amount of toxic metal is present, eventual death of the organism.

The two important factors in heavy metal toxicity are bioaccumulation and bioconcentration. Bioaccumulation, refers to the ability of organisms (typically microbes and plants) to accumulate dissolved metal ions (or possibly metals bound to small molecules) from the environment onto their surfaces or into their cells. Toxic heavy metals ingested by higher organisms (animals) with their food source are often retained (not excreted) and their concentration in living tissue is magnified over that present in their food and environment. This process can be called bioconcentration. The overall effect of bioaccumulation and bioconcentration can lead to heavy metal toxicity in higher organisms. It should be noted that no standard terminology has evolved, and other terms, particularly biosorption, are often used in the literature to denote such processes. Here, the term "biosorption" is restricted to the more or less reversible, metabolism independent, binding of metals to cell surfaces. "Bioaccumulation" is used here to refer to all biological processes which lead to the removal of dissolved, or even particulate, metals from the environment. Bioaccumulation is the primary cause for the overall process of bioconcentration of metals from the environment into higher organisms and eventually humans.

We use the term "bioremoval" for the engineered process that removes heavy metals from waste or contaminated environments. Bioremoval differs from "bioremediation" in that the latter deals with the biochemical/microbiological destruction of toxic agents. In the case of heavy metals, destruction is not feasible and they must be recovered and either safely disposed of or recycled.

Higher plants exhibit bioaccumulation, and many biological macromolecules (lignins, polysaccharides, chitin, even peat) can bind heavy metals. However, processes based on plants can not be readily engineered, and most biological macromolecules are either too difficult to work with or not sufficiently powerful for most applications. Bioremoval by microorganisms, either living or dead, provides the greatest potential for future applications and is the focus of this report.

2.2 Comparison of Bioremoval with Conventional Technologies

The principal methods presently used for removing heavy metals from wastewaters are caustic (lime or hydroxide) precipitation and ion exchange. Other methods used include sulfide precipitation, activated carbon adsorption, solvent extraction, reverse osmosis and a number of other techniques (Brauckmann, 1990). All of these have severe limitations that highlight the need for the development of new technologies to protect and clean-up the environment. In this section, we briefly describe some of the limitations of conventional heavy metal removal methods and review available data comparing these methods to bioremoval.

Precipitation techniques are capable of substantially reducing metal concentrations in wastewaters, but the concentration of metals in the supernatant is still often higher than permissible discharge limits (Kuyucak, 1990). Costs of precipitation processes can be very high because large amounts of chemicals are required and the operation requires considerable attention to compensate for changes in waste characteristics (flows, pH, solids contents, etc.). Another major drawback of precipitation processes is the large amounts of metal-containing toxic sludges that are generated. These sludges can become a significant long-term waste disposal problem and legal liability for the waste generator.

Ion exchange is frequently used as a polishing step following lime precipitation and other treatments. Ion exchange resins are expensive, subject to chemical degradation, have little resistance to thermal and osmotic shock, and are fouled by organic materials and/or precipitates such as calcium sulfate or ferric hydroxide (Kuyucak, 1990). The strong affinities for specific metals by ion exchange resins typically cause more weakly bound metals to be easily displaced by the more strongly bound ones and thus, generally poor performance for mixed waste and wastewaters containing high levels of non toxic ions such as Ca^{++} and Mg^{++} . Another problem is that the elution of heavy metals from ion exchange resins is normally difficult. Typically, the sulfuric acid regeneration treatment does not remove all of the metal, and the subsequent water wash results in considerable amounts of additional metals coming off, which result in the production of a rather dilute metal solution requiring additional treatment or disposal.

In contrast, bioremoval processes are generally free from the above limitations. However, despite extensive information on the binding of heavy metals to microbial biomass, numerous discussions of the potential applications of microorganisms for metal binding, and even one commercial operation in which microbial biomass is being used for heavy metal removal, there are few comparative studies of microbial heavy metal concentrating processes with conventional technologies.

Brierley et al (1986) qualitatively compared bioremoval using immobilized inert biomass to other technologies based on fundamental considerations (Table 1). Basically, they concluded that bioremoval is more versatile than other technologies in coping with variations in waste flows (e.g., pH, other metals, etc.) and can reduce metal concentrations to lower levels than most other technologies.

Table 1. Comparison of Various Heavy Metal Treatment Technologies
(Adapted from Brierley et al., 1985)

PROCESS	ABILITY TO RESPOND TO VARIATIONS IN:					RESIDUAL HEAVY METAL CONC.
	Heavy Metal Concentration	pH	Suspended Solids	Dissolved Organics	Other Heavy Metals	
Caustic Precipitation	poor	poor	OK	OK	OK	>1ppm
Sulfide Precipitation	OK	poor	OK	OK	OK	>1ppm
Ion Exchange	OK	some	poor	poor	some	<1ppm
Electrodialysis	OK	some	poor	poor	some	>1ppm
Reverse Osmosis	OK	some	poor	poor	some	>1ppm
Bioremoval	OK	OK	OK	OK	OK	<1ppm

C. Brierley (personal communication, 1990) compared a bacteria-based biosorbent to an ion exchange resin (IRC 718) in terms of heavy metal removal with actual wastewater samples (Table 2). She found that in all wastewater samples tested, bioremoval was superior or similar to ion exchange.

Table 2. Relative Effectiveness of Bioaccumulation vs. Ion Exchange (data in mg/l)

Metal	<u>Wastewater Sample I</u>			<u>Wastewater Sample II</u>		
	<u>Influent</u>	<u>Effluents</u>		<u>Influent</u>	<u>Effluents</u>	
		<u>Biosorbent</u>	<u>IRC718</u>		<u>Biosorbent</u>	<u>IRC718</u>
Ni	8.74	0.29	1.04	9.71	0.53	0.35
Cu	43.7	2.02	8.55	24.98	3.37	3.31
CrIII	7.23	1.56	5.33	42.1	3.71	16.29
Cd	0.46	<0.04	0.09	<0.04	<0.04	<0.04
Zn	6.8	0.47	1.19	21.2	0.6	1.28

Tsezos and Volesky (1981) showed that the ion-exchange capacity of the microbial cell wall can be greater than that of commercial ion-exchange resins. They compared the U and Th biosorption ability of fungal biosorbents to ion exchange resin IRA-400 and activated carbon in laboratory-scale experiments. The microbial biomass accumulated about three times as much U and Th than the conventional methods at 5 and 30 mg/l residual concentrations.

Darnall et al., (1987) compared immobilized algae (*Chlorella pyrenoidosa*) with the ion exchange resin PAZ-1 (Sela Corp.), that has a high binding capacity for gold and other precious metal ions. Columns containing equal bed volumes of algae and ion exchange resin were washed with 0.1M HCl and then 0.41 mM HAuCl₄ solution at pH 1.5 was applied. Both columns were then washed with 10 bed volumes of 0.1M HCl and subsequently eluted with stripping solution (thiourea/perchloric acid/HCl). After washing again, they were subjected to additional rounds of metal binding. Results are shown in Table 3.

Table 3. Au Absorption by Immobilized Algae and Ion Exchange Resins
(0.41 mM Au solution applied and recovered) (Adapted from Darnall et al., 1987)

<u>Cycle Number</u>	<u>Immobilized Algae</u>		<u>Ion Exchange Resin PAZ-1</u>	
	<u>Eluate % Removed</u>	<u>Stripped % Recovered</u>	<u>Eluate % Removed</u>	<u>Stripped % Recovered</u>
1	99.5	88	98	78
2	95	83	73	54
3	96.5	88	77	61
4	92.5	85	68	58
5-10 (Avg.)	96	84	70	50

The data in Table 3 show that the initial (first cycle) binding by the algal biomass was greater (99.5% vs 98%) and that more gold (88% vs 78%) was recovered. More importantly, subsequent cycles demonstrated a major advantage of the algal biomass over the ion exchange resin in terms of Au removed and recovered over 10 cycles. Thus, the immobilized algae exhibited significant advantages in this application. Similarly, the alga *Sargassum natans* selectively sequesters gold from industrial solutions. The algal biomass has uptake capacity close to 40% of its dry weight and outperforms ion exchange resin IRA-400a for this application (Kuyucak and Volesky, 1988).

In addition to providing superior retention and elution, algal biosorption materials are superior to ion exchange resins because ions of common elements such as Ca and Mg cause much less interference with heavy metal removal. Thus, the waste solution does not need to be subjected to a preliminary water softening process prior to heavy metal removal (Darnall, et al., 1987). Finally, Darnall et al (1987) demonstrated that by judicious use of pH and other conditions, the algal biosorbent selectively released specific metals, such that they could be recovered independently. This is a valuable feature that is not achievable with any conventional heavy metal removal processes.

Overall, the limited data comparing bioremoval with conventional heavy metal removal methods indicate that several potential advantages are possible with bioaccumulation based processes including the following:

1. Use of naturally abundant renewable biomaterials (i.e., algae) that can be cheaply produced;
2. Ability to detoxify and clean large volumes of wastewater due to rapid kinetics and high capacities;
3. High selectivity in terms of removal and recovery of specific heavy metals;
4. Ability to handle multiple heavy metals and mixed waste;
5. High affinity for toxic heavy metals, facilitating the treatment of wastewaters with low metal concentrations and reducing residual metals to below 1 ppb in many cases;
6. Less need for additional expensive process reagents which typically cause disposal and space problems;
7. Operation over a wide range of physicochemical conditions including temperature, pH, and other ions (including Ca^{++} and Mg^{++}), reducing the need for water softening and/or other pretreatments;
8. Relatively low capital investment and low operational costs; and
9. Recovery of heavy metals from the biomass with greatly reduced generation of hazardous sludges.

Of course, for a particular biomass, process, and application, not all of these potential advantages would be applicable in equal measure. For example, for the removal of low levels of metals (e.g., in the 10 to 100 ppb range), the amount of metal absorbed to the biomass, or its regenerability may not be as crucial as the affinity of the biomass for the metal. Thus, treating a billion liters of wastewater containing 10 ppb of metals would require one ton of biomass if the metal binds at 1% of the dry weight (a concentration factor of one million). This amount of biomass could probably be sacrificed without need for re-use in such a process. However, to remove 10 ppm of metal, even at 10% level in the biomass, would require 100 tons of biomass and would probably not be practical without biomass re-use.

In the case of a high concentration (e.g., >10 ppm) of heavy metal waste that must be reduced to very low concentrations (e.g., 1 ppb or less), a two stage process would probably be most appropriate. The first stage would emphasize the capacity of the bioaccumulating agent, the ability to release the metals from the biomass easily and in a concentrated fashion, and the re-utilization of the biosorbent. The second stage would emphasize the affinity of the biosorbent, to reduce the residual metals to very low levels. Indeed, such a "finishing" biosorbent stage could be used in conjunction with more conventional technologies.

Other factors to consider in process design are the flow rates, the variations in the process waste, other metals and ions, and the performance criteria of such processes. Thus, in practice, each application must be considered on its own merits, and the specific advantages and disadvantages evaluated for both the conventional technologies and the bioaccumulation processes.

One of the major differences between bioaccumulation and conventional heavy metal methods is that it is possible to manipulate the bioaccumulation capabilities (e.g. specificities, capacities, affinities, etc.) of biomass through culture conditions during growth (e.g., nutrient limitations, other metals present in the media, etc.) and through genetic means (selection of high metal binding organisms and even mutants). Although this gives bioaccumulation even greater potential advantages over conventional methods than discussed above, much additional R&D is required in this area.

In conclusion, bioremoval is economically feasible and has many features technically superior to conventional heavy metal removal techniques.

2.3 Mechanisms of Bioremoval

Bioremoval studies with microorganisms are relatively easy to carry out. An actual, or a closely simulated, challenge solution is incubated, normally with shaking, with a particular biomass source for sufficient time to establish an equilibrium or approach an end point in the bioremoval process. The biomass is then separated from the solution, typically by centrifugation or filtration, and the metal concentration remaining in solution and/or the amount of metal bound to the biomass are determined. To obtain kinetic data, the experiments are carried out as a function of time. To determine the affinity of the metal for the biomass, the concentration of the metal is varied. Other experimental variables (pH, presence of other ions, biomass concentrations, various microbial biomass sources, etc.) are also investigated in such studies.

Bioremoval processes can be broadly divided into two classes: those that require living (metabolically active) microbial biomass and those that use inert (dead) biomass or specific microbial biomass components (e.g. cell walls). Living microbial systems often transport the metals inside the cells (absorption) and dead biomass primarily adsorbs the metals to cell surface components. However, this generalization is not always valid: living cells often behave like inert biomass and the major effect observed is a reversible adsorption of the metal to the cell surface. In some cases, surface adsorption of heavy metals requires active cell metabolism. In a few examples, even dead biomass will concentrate metals intracellularly.

Because of the fewer complications introduced by the use of inert biomass (e.g. dried or heat-killed cells), these have been the subject of much of the research, and most of the present commercial developments, of this technology. Inert biomass can be handled in ways very similar to ion exchange or activated carbon systems: the biomass can be stored until required and used in the same type of canisters or columns used in conventional processes.

Inert biomass often adsorbs metals to the surface cell walls in high amounts, with some specificity and high affinity, under conditions (temperature, pH, etc.) similar to those tolerated by chemical processes, and in a reversible manner: the adsorbed heavy metals can be eluted (usually by an acid or basic solution) and the biomass reused several times. Thus, bioremoval systems using inert biomass sources are comparable to conventional metal removing processes and their technical evaluation would be based on similar factors: capacity, equilibrium metal concentrations, specificity, reuse, scale-up characteristics, and costs.

By contrast, the use of living microbial biomass introduces significant complications. Living biomass is relatively sensitive to environmental conditions, such as temperature, pH, and toxic metal ions. The microbial cells must be supplied with some source of energy to maintain metabolism. The storage (shelf life) of the microbial biomass is limited, normally requiring that growth of the microbial culture be closely coupled with the operation of the bioaccumulation system. Reuse of the microbial biomass is usually not feasible.

Despite these apparent drawbacks, living cells often accumulate metals from much lower concentrations (ppb or even lower) than normally observed with inert biomass, with higher concentration factors and greater specificities for a particular toxic metal, even in the presence of other metals and ions. These characteristics suggest that bioremoval processes involving living organisms should be considered in cases where very low concentrations of specific metals or radionuclides must be removed.

There are several mechanisms by which bioremoval can occur, whether the cells are living or dead. These include:

- action of cell walls as ion exchange materials;
- chelation, precipitation and even crystallization of heavy metals on cell surfaces;
- bioprecipitation of metals by metabolically generated H_2S or other agents;
- active uptake and intracellular storage of metals;

- metabolism dependent oxidation or reduction of metals and their precipitation (intra/or extracellularly); and
- complexing of metals by more or less specific binding agents excreted by or present in the cells.

The actual mechanism(s) involved in bioremoval processes is uncertain in many cases and several mechanisms may be involved simultaneously or sequentially. Thus, simple mechanistic distinctions are usually not possible and the literature data must be interpreted in terms of basic process parameters: equilibrium concentrations (binding isotherms), removal rates and kinetics, capacity factors, interferences by other ions, effects of pH and temperature, etc. In many cases, only a few of these are reported and comparison between different literature reports is difficult, if not impossible, as experimental results are very dependent on the exact conditions (in particular pH and other ions present in the challenge solutions) under which the experiments are carried out. Also, very large variations, up to several orders of magnitude, in bioremoval results are routinely observed with rather subtle changes in biomass (e.g., different strains of a single species and even the same strain grown under different conditions). Most of the applied R&D in bioaccumulation is therefore empirical in nature. Moreover, most of the literature data on removal and concentration of heavy metals deals with defined, usually single metal, solutions. In actual waste streams, multiple metals and high, often variable, concentrations of other ions can interfere with, or at least significantly affect, the bioremoval processes.

In conclusion, the available data in the literature must be interpreted with caution and any specific application must, at least for the foreseeable future, be based on both laboratory and larger scale studies using specific biomass sources, heavy metals in actual or simulated waste solutions, and environmental conditions as similar as possible to those that will be encountered in practice. A key issue is the selection of the biomass.

2.4 Selection of the Microbial Biomass

Bioremoval studies have been carried out with bacteria, fungi (including yeasts) and microalgae. Bacteria and fungi are heterotrophic - they require preformed organic substrates for growth, while algae are normally autotrophic - they can grow using sunlight and carbon dioxide as sources of energy and carbon.

As already indicated, much of the research on the development of practical bioremoval processes has been carried out with inert (dead) biomass. Because of the relatively greater difficulties of using living biomass, some authors have concluded that living microbial cells, would present insurmountable obstacles in the development of practical processes. However, living microbial processes have been used in large-scale treatment of municipal and industrial wastes for over a century, and there is no *a priori* reason to suppose that they could not be adapted to the requirements of effective metals removal. Indeed, a considerable body of literature suggests that living biomass systems have significant advantages over the use of dead biomass in the removal of low levels of heavy metals. Thus, both dead and living microbial biomass should be considered in bioremoval process development.

Another issue is the nature of the microbial biomass to be used in bioremoval processes. Considerable work has been done with each of the three principal groups of microorganisms - bacteria, fungi (including yeasts), and microalgae. Although some generalizations can be made, for example, that gram negative bacteria (i.e., *Escherichia coli*) do not bind as much metal as gram positive bacteria (i.e. *Bacillus subtilis*), in general, variations among strains of a single species can be as large as variations between genera and even between microbial groups. Subtle distinctions in cell wall surface chemistry and metal transport systems greatly affect metal binding by microorganisms. As cell surface chemistry changes with changing environments, it is not surprising that microbes cultured under different conditions (e.g., different limiting nutrients) exhibit large variations in their metal binding capabilities.

Thus, there is little to a priori guide the selection of the most suitable biomass for a specific application. One of the objectives of this literature review was to identify promising microbial species for use at the SRS. However, the literature does not allow firm conclusions about the most useful type of biomass for specific bioremoval applications: too few studies have compared different microbial biomass sources from the wide variety of possible sources in side by side trials, to allow at present a clear choice between the various biomass types. Thus, the selection of biomass sources for the development of novel bioaccumulation applications and processes must be based on considerations other than a proven superiority in metal bioaccumulation by specific types of microorganisms.

There have been basically two approaches in selection of microbial biomass sources for bioaccumulation studies. The first alternative was to test various sources of biomass commercially available, usually as byproducts of other activities, such as food fermentations, the pharmaceutical industry, or wastewater treatment. Normally one or a few such biomass sources were tested under fairly exhaustive conditions (e.g., various pH values, presence of other ions, metal concentrations, kinetics, etc.). The second alternative was to screen large numbers of different microbes under more or less standardized conditions, to identify strains that were clearly superior in metal bioaccumulation.

The first approach, using readily available, commercially produced biomass sources, has considerable merit during the start-up of commercial bioremoval ventures: it minimizes up-front capital costs in biomass procurement. This is the approach favored by the only current commercial venture in the U.S., Bio-Recovery Systems, Inc., which uses commercially available microalgae (*Chlorella* and *Spirulina*) in their proprietary biosorption systems. However, extensive screening studies have indicated that different microbial biomass sources exhibit differences in the binding of particular metals by several orders of magnitude. Thus, processes which depend on an already available source of biomass, grown for purposes other than bioaccumulation, are unlikely to select the most suitable microbial strain and growth condition for such a process.

By using biomass sources specifically selected and cultivated for particular applications, the currently available products and processes could be greatly improved. Although this would increase initial start-up costs, in the long term, as such processes become more widely used, this would actually reduce costs due to the improved performance possible with such selected biomass sources. Furthermore, the emphasis on the use of inert biomass systems has neglected the greater potential of using living biomass sources in such processes. Thus, a major conclusion from the literature review (see Volume II) is that for advanced applications, such as would be required at the SRS, attention should not be limited to the use of currently available biomass sources or processes.

The question arises of how to design an R&D program with a manageable number of microbial species and strains, and biomass cultivation conditions. Essentially, the question is whether representative examples of each group of the different microbial types should be used in a screening program or whether attention should be concentrated on a particular type of microbial biomass.

2.5 Rationale for Selection of Microalgae.

Because of the practical inability of any research program to deal with all possible microbial biomass types, a rational basis for restricting consideration to a limited number of biomass sources is required. Although there is not sufficient evidence to exclude any group of microbes, it was concluded that the best choice for a bioremoval program at the SRS is the use of microalgae. The factors supporting such a selection are listed below (see Volume II for supporting information and literature citations).

1. Microalgae have been the subject of extensive R&D for metal binding. These studies revealed that microalgae were often better than other microbial biomass sources.
2. Microalgae, being at the beginning of the aquatic food chain, are responsible for much of the bioconcentration of heavy metals and radionuclides that ultimately causes a variety of environmental impacts from these toxic agents. These same processes can be used to remove these metals before they cause damage to higher components of the food chain.
3. Inert microalgae biomass is used in the only current commercial applications of biosorption (ion exchange type) materials for heavy metal removal from wastewaters.
4. Microalgae cells have relatively low affinities for Mg and Ca, allowing heavy metals to be removed without the need for water softening (Darnall et al., 1986a).
5. Microalgae can sequester heavy metals by the same adsorption and absorption mechanisms as other microbial biomass as well as by the formation of phytochelatins which they synthesize in response to heavy metal stress (Gekeler et al., 1988).
6. Microalgae use light as an energy source, facilitating the maintenance of metabolism in the absence of organic carbon sources, required by bacteria or fungi. Thus, the use of metabolically active microalgae systems may be more readily achieved.
7. Microalgae cultures can be cultivated in open ponds or in large-scale laboratory culture, providing a reliable and consistent supply of biomass for such studies and eventual scale-up work.
8. Considerable experience exists at SRS with microalgae cultures. A pilot algaculture process being developed by SRL at this time provides an excellent synergism to bioremoval studies.

In combination, these factors justify focusing a future R&D project at the SRS on microalgal bioremoval.

2.6 State-of-the-Art of Microalgae Bioremoval

As stated above and reviewed in more detail in Volume II, microalgae have been subjected to extensive bioremoval research, both with living algae and inert biomass. When algae are contacted with heavy metals a rapid, metabolism independent, reversible, adsorption ("biosorption") is generally observed, usually complete within 10 minutes. With living cells a slower, longer lasting, normally metabolism dependent, irreversible, metal uptake reaction (absorption) often follows the initial phase.

A typical example of binding of heavy metals to algal surfaces was recently described by Xue et al. (1988) who demonstrated that the kinetics of adsorption and uptake of Cu(II) by the green alga Chlamydomonas reinhardtii involved the establishment of relatively fast adsorption equilibrium with the surface, followed by a slower diffusion-controlled uptake into the cytoplasm of the cell.

In some case, only the metabolism dependent mode of bioaccumulation has been observed. For example, Maeda et al. (1985) reported that arsenic bioaccumulation by the green alga Chlorella vulgaris occurred only when living cells were involved. Living cells bioaccumulated up to 5% arsenic (by dry weight of the algae) but no arsenic was bioaccumulated when cells had been pretreated with a respiratory inhibitor or heat-killed. Similarly, Bender and Ibeanusi (1987) reported that passive adsorption on cell surfaces was not a primary mechanism in the long-term uptake of lead by the filamentous blue-green alga Anabaena. Lead uptake was increased by carbon dioxide additions and by additions of other nutrients. Metabolic activities can even be involved in the deposition of metals on the cell surface, as observed by Ahlf (1988) with Cyanidium caldarium, where a redox sensitive metabolic process resulted in relatively large amounts of metals being precipitated on the surface of the cell wall. Microalgae can also sequester heavy metals by the formation of phytochelatins which they synthesize in response to heavy metal stress (Gekeler et al., 1988). Phytochelatins are peptides produced only by algae and higher plants. They are analogous to the metallothionein proteins produced by fungi and animals in response to heavy metal stress. A wide variety of heavy metals, well beyond the range known to induce metallothioneins, result in the synthesis of phytochelatins by algae (Gekeler et al., 1988).

The relative amount of metal uptake due to the two basic processes (adsorption and absorption) depends on the algal strain used, characteristics of the solution including concentration of the metal, and the status of the cells. The physicochemical characteristics of the solution being treated, particularly pH and redox potential, are major factors influencing algal bioaccumulation. Generally, algal cell walls act as polyfunctional cation exchangers with negatively charged ligands depending on the pH and metal species. Adsorption on cell surfaces typically decreases with pH.

In the evaluation of microbial bioremoval processes, the key parameter of interest is the concentration factor (CF) as a function of residual (equilibrium) metal ion concentration. This determines the amount of biomass required to treat a particular waste water to a desired level. However, in most literature reports insufficient data is provided to obtain this information. Often, only the initial (not final) metal concentration is reported, or the amount of biomass used in the experiment is either not stated or provided in units not easily convertible to dry weights.

For example, Hart and Scaife (1977), studying bioremoval of Cd by live cells of Chlorella pyrenoidosa, reported a CF of about 4000 based on the initial amount of metal added. If the calculation were made on the residual metal concentration (about 0.5 mg/l), the concentration factor would have been about 2 million, as the reported amount of metal present on the biomass equaled the amount of organic dry weight. They demonstrated that this metal uptake involved an energy intensive metabolic process, with the algae being unable to accumulate Cd in the dark. Subsequently, Hart et al. (1979) demonstrated that Cd uptake was inhibited by Mn (but not Zn or Co), suggesting that Cd was taken up by the cells through the Mn transport system. By contrast, with the species Chlorella fusca, competition of Cd uptake by Zn suggested that the two metals share a common uptake system. Thus, bioremoval can be species, and perhaps even strain, specific.

In contrast to the very high CFs found by the above researchers (Hart and Scaife, 1977), Sakaguchi et al. (1979), using the same algal species (but a different strain and experimental conditions), observed a concentration factor of slightly below 4000. Although the cells were presumably living, but not actively growing, uptake was not due to metabolic activity as it was independent of inhibitors and the Cd was released by EDTA. The comparison of these two reports, with approximately a 500 fold difference in uptake and affinity, most clearly demonstrates the relative power of active vs. inactive biomass, as well as the large variations encountered between different literature reports, even when dealing with the same microbial species and metal.

Probably the most comprehensive study of metal uptake by living microalgae was that of Hassett et al. (1981) who investigated bioaccumulation using microtitre dishes, which allow up to 96 tests to be carried out simultaneously in one experiment. They tested 11 different algal strains for bioaccumulation of three metals (Cd, Pb, and Hg) over a range of pHs. Old cultures had very low CFs, less than one tenth (in most cases less than 1/100th) those of younger (growing) cultures. This is a general observation. Concentration factors varied substantially with different metals, pH, and algal strains, ranging from less than 100 to almost 100,000. The experiments were carried out in the dark, which probably reduced metabolically dependent metal absorption relative to surface adsorption (biosorption) of the metals.

In a comparative study of living vs. heat killed Chlorella cells, Nakajima et al. (1981) found that the two were generally comparable, and in the case of UO_2^{++} , there was substantial removal of the metal. Concentration factors of up to 4000 were reported. Other work by the same group (Horikoshi et al., 1979) had demonstrated similar results with no major differences between living and dead cells, and most of the U ion adsorbed to the cell wall material.

Chlorella vulgaris (but not C. pyrenoidosa) was able to accumulate over two thirds of the Al from a 45 ppb solution. This Al could be eluted at pH 1.0 and the biomass reused several times (Zimnik and Sneddon, 1988). Les and Walker (1984), working with the sheath forming blue-green alga Chroococcus parvus, tested bioaccumulation of Cd, Cu, and Zn and observed, typically, CFs of about 4000. The algal cells were living during the experiments. Other workers have reported even higher CFs for Zn (Failla, 1977).

Very high concentration factors have been reported for some radionuclides. However, most of these reports do not provide information about the actual mass amounts of these metals present or the residual radioactivity after the binding experiment, which makes it difficult to determine the actual capacity of the algae for these materials. For example, Harvey and Patrick (1967), working at the SRS, measured concentration factors (CFs) for carrier-free radioisotopes of Zn, Cs, and Sr at very low concentrations. They observed CFs with Zn of up to 3700 for species of green algae and up to 21,500 for diatoms, with rapid desorption after removal of the radionuclide. For the other isotopes the concentration factors were much lower. Fisher et al. (1983), working with seven marine microalgae and radioisotopes of Pu, Am, and Np, observed CFs of greater than 100,000 with living cells, although bioaccumulation was ascribed to passive adsorption by the cell walls. Diatoms had higher CFs than green or blue-green algae.

Tarifeno-Silva et al. (1982) studied the concentrations of 15 heavy metals in successive stages of artificial food chains composed of algae, herbivorous crustaceans, and carnivorous fish. These food chains were grown in secondarily treated chlorinated/dechlorinated domestic wastewaters. Bioaccumulation of heavy metals occurred mainly in the algae (CFs of 500-30,000). Later stages in the food chains showed successively lower accumulations (CFs of 30-6000 for cladocerans and 4-1600 for fish).

Table 4 summarizes the above discussed studies and their reported CF values. It must be cautioned that concentration factors must be determined over a range of residual metal concentrations to allow an evaluation of the utility of the biomass for bioremoval processes. Also, the CFs are sensitive to the exact experimental conditions (pH, other ions, etc.) and thus not directly extrapolatable to actual wastewaters. However, the data does indicate the great power of some of the microalgae in specific metal removal processes and the great variation between biomass sources, metals, and experimental conditions. This suggests that applied research is required to identify the most suitable algal strain and conditions for any particular metal and waste material.

Table 4. Heavy Metal Uptake by Algae

CONCENTRATION FACTOR	METAL(S)	TYPE OF ALGAE	REFERENCE
3,700	Zn	Green algae	1
21,600	Zn	diatoms	1
ca. 4,000	Zn, Cu, Cd	<u>Chroococcus parv</u>	2
2,000,000	Cd	<u>Chlorella pyrenoidosa</u>	3
<4,000	Cd	<u>Chlorella pyrenoidosa</u>	4
1,000-100,000	Cd, Pb, Hg	various spp.	5
4,000	U	<u>Chlorella</u>	6, 7
>100,000	Pu, Am, Np	various spp.	8
500-30,000	Various	various spp.	9

References: 1 = Harvey & Patrick (1967) 2 = Les & Walker (1984)
3 = Hart & Scaife (1977) 4 = Sakaguchi, et al. (1979)
5 = Hassett et al. (1981) 6 = Nakajima et al. (1981)
7 = Horikoshi et al. (1979) 8 = Fisher et al. (1983)
9 = Tarifeno-Silva et al. (1982)

The most extensive research on bioaccumulation by dead microalgal biomass has been carried out by Darnall and co-workers at the University of New Mexico at Las Cruces and Bio-Recovery Systems, Inc. (Darnall et al., 1986b; Greene et al., 1986; Bedell and Darnall, 1989; Darnall et al., 1988; Darnall and Bedell, 1989). Using two commercially available sources of dried algae (Chlorella and Spirulina), they documented the biosorption of many heavy metals from actual and simulated wastewaters. A major part of this work was in developing suitable immobilization procedures to allow the biomass to be used in column reactors, similar to ion exchange columns. These studies led to the first successful commercialization of biosorbent materials, through Bio-Recovery Systems, Inc.

2.7 Bioremoval Process Development

The simple bioremoval batch tests in which the challenge solution is contacted with the microbial biomass in shake flasks, are not sufficient for development of waste remediation processes. Practical bioremoval processes must be able to contact the metal-laden solution with the microbial biomass in a continuous process and, in addition, be able to readily separate the microbial biomass from the liquid phase. The conventional laboratory procedures used to accomplish the latter, centrifugation and filtration, are not adequate for the requirements of practical processes, both in terms of economics and ease of operations. The microscopic nature of the microbial cells makes separation of the biomass a difficult and crucial aspect of process development.

The requirement of easy separation and continuous processing can be readily achieved by immobilizing the microbial cells on some type of support, thereby converting the biomass into an organized macroscopic material similar to activated carbon granules or ion exchange beads. Immobilization processes for microbial cells can involve chemical (covalent or ionic) binding of the cells to some type of otherwise inert surface or the physical trapping of the cells into a permeable matrix material. The cells can even be aggregated together, through chemical or biological processes. Such immobilization processes can involve a large number of different support or matrix materials, chemical reactions to couple the cells to the supports, or cultivation conditions, to result in a biological attachment of the cells to such surfaces ("biofilms") or each other ("flocs").

Immobilized cells can then be used in columns or similar contacting systems (e.g., rotating biological disks, expanded bed reactors, trickling filters, etc.) to achieve continuous processes. It should be noted that such processes, using living microbial biomass, are already extensively used in large-scale wastewater treatment plants: activated sludge (flocs), trickling filters, rotating biological contactors, and nitrification/denitrification plants. Thus, immobilization processes need not be restricted to artificial chemical binding or physical entrapment of dead biomass and can be used with living microorganisms. The development of superior, or at least proprietary/patentable, immobilization processes is a major R&D activity in the commercial sector. However, the choice of the immobilization process is not as critical as that of the microbial biomass.

There is one approach to the biomass separation problem that would not require any specific processing of the biomass: use of microalgal cultures that either grow naturally in the form of biofilms or, even better, filamentous or colonial organisms that can be easily separated after the contacting step via microstraining or sedimentation. Indeed, such approaches would be favored over the currently used immobilization techniques which result in a significant decrease in the rate and extent of metal absorption of the biomass because of diffusion limitations in the immobilized biomass.

The use of dispersed filamentous cells or colonies exposes much larger surface areas to the bulk liquid and, thus, results in higher rates, and greater capacities of metal binding. Therefore, in the proposed SRS research project, filamentous, and colonial microalgae would be specifically investigated. These types of microalgae are already being investigated in ongoing algaculture research at SRL.

3.0. POTENTIAL APPLICATIONS OF BIOREMOVAL AT THE SRS

Although a detailed inventory of potential sites at the SRS that could benefit from bioremoval processes has not been conducted, a preliminary survey identified several specific areas for applications:

1. M Area (Reactor Fuel and Target Fabrication Facilities)

Specific applications include reducing discharges of heavy metals to Tims Branch, recovering uranium from contaminated sediments, and removing heavy metals (especially Al) from the M-Area effluent stream system including Steeds Pond.

2. F and H Areas (Chemical Separation Areas)

Specific problems include mercury removal from process streams and heavy metal/radionuclide decontamination of the seepage basins.

3. Reactor Areas (R, P, K, C, and L Areas)

The opportunities here include decontamination of the disassembly basins and decommissioning of seepage basins.

4. Photographic Waste

There are several locations at the SRS where silver contaminated wastes are generated. Some, if not all, of these are particularly well suited for treatment with bioaccumulation processes.

5. Coal Pile Leachate

The coal pile leachate and ash basin runoff waters are relatively high in various heavy metals. These could potentially be treated with bioaccumulation processes.

6. TNX

Specific problems include removal of trace metals and radionuclides from contaminated groundwater.

7. Miscellaneous Ground and Surface Waters

Bioaccumulation processes could be used to clean-up a variety of existing ground and surface waters at the SRS containing measurable concentrations of heavy metals and/or radionuclides.

A more detailed inventory of potential applications is required. However, the preliminary assessment clearly identified several possibilities where novel technologies could be used in the decontamination and clean-up efforts at the SRS.

Although bioremoval R&D of interest to SRS could be carried out at some facility remote to SRS, only an onsite project is likely to be able to integrate the bench-scale and pilot plant work in an efficient manner and closely focus on the actual problems at SRS, rather than more generic and basic problems. Such a research effort is outlined in the next Section.

4.0 RESEARCH PLAN

The research and development plan described herein has two phases. Both phases could be carried out onsite.

Phase 1: Proof of Concept Stage

- (A) Select 3-6 specific aquatic systems at SRS where the removal and/or recovery of heavy metals would be desirable.
- (B) Prepare challenge solutions that mimic as closely as possible the waters identified in (A), without, at least initially, the radioactivity that may be present in the actual waters.
- (C) Select 6-10 algal strains for initial testing.
- (D) Test and compare the heavy metal sequestering abilities of the selected microalgae with the selected challenge solutions.
- (E) Identify in detail the quantities and compositions of the various potential metal/radionuclide containing wastes throughout the SRS and prioritize these in terms of potential applications of bioremoval technology.

The decision to proceed to the developmental stage (Phase 2) of the proposed research plan would be based on the findings of Phase 1.

Phase 2: Development Stage

- (A) Based on the results of the Phase 1 experiments, develop process concepts using microalgae biomass to achieve specific process goals, in terms of amounts of radionuclides or heavy metals removed, contacting conditions, biomass handling (regeneration, metal/radionuclide elution, biomass disposal) and ultimate waste disposal.
- (B) Develop the process concepts to the laboratory bench scale, using both simulated and actual waste materials. Determine possible scale-up problems with such systems.
- (C) Pilot test one or more of the proposed concepts at SRS.
- (D) Commercialize the developed technology by contracting for commercial installation at SRS of an actual operating system as well as through technology transfer to other DOE facilities and private industry.

5.0 CONCLUSIONS

Based on this review of the literature (see also Volume II), we conclude that bioaccumulation can be developed into new and powerful bioremoval processes for treating waters contaminated with heavy metals and radionuclides. Development of such practical applications requires specific process R&D for each particular wastewater and application. Such process R&D would involve selection of a suitable microbial species and growth conditions and development of an engineered bioreactor in which the biomass can be contacted with the waste solution, followed by biomass separation and metal recovery or disposal. This report identifies microalgae as the organisms of choice in a future R&D project at the SRS. Because of the complex and manifold applications which could be foreseen at the SRS and other DOE sites, the best approach is to carry out such R&D at or near the actual site where the process is to be applied.

6.0 LITERATURE CITED

- Ahlf, W. "Recovery of Metals from Acid Waste Water by Cyanidium caldarium", Appl. Microbiol. Biotechnol. 28:512-513 (1988).
- Ahlf, W., U. Irmer, and A. Weber. "Accumulation of Lead by Fresh Water Algae Under Various Conditions", Z. Pflanzenphysiol 100:197-207 (1980).
- Bedell, G.W., and D.W. Darnall, "Immobilization of Non-Viable, Biosorbent, Algal Biomass for the Recovery of Metal Ions", in Volesky, B. (ed.), Biosorbents and Biosorption Recovery of Heavy Metal Ions, CRC Press, (1989, in press).
- Bender, J. and V. Ibeanusi, "Effects of Supplements on the Bioaccumulation of Lead in Anabaena spp.", Bull. Environ. Contam. Toxicol. 39:209-213 (1987).
- Brauckmann, "Industrial Solutions Amenable to Biosorption", in Volesky, B., Editor, Biosorption of Heavy Metals, CRC Press Inc., Boca Raton, Florida (1990).
- Brierley, J. A., G. M. Goyak, and C. L. Brierley, "Considerations for Commercial Use of Natural Products for Metals Recovery", in Eccles., H., and S. Hunt, (eds.), Immobilization of Ions by Bio-Sorption, Ellis Horwood, Ltd. (1986).
- Darnall, D.W., and G.W. Bedell, "Heavy Metal Ion Recovery Using Biological Biosorbents", Presented at the Symposium Biotechnology in Minerals and Metal Processing, held in Las Vegas, Nevada, Society of Mining Engineers, (1989).
- Darnall, D.W., B. Greene, and J. Gardea-Torresdey, "Gold Binding to Algae" in Kelly, D.P., and Norris, P.R. (eds.), Biohydrometallurgy 1987, Warwick, Science and Technology Letters, London pp, 487-498 (1988).
- Darnall, D.M., B. Greene, M. Hosea, R.A. McPherson, M. Henzl, and M.D. Alexander, "Recovery of Heavy Metals by Immobilized Algae", in Thompson, R. (ed.), Trace Metal Removal from Aqueous Solution, The Industrial Div Royal Soc. (1986a).
- Darnall, D.W., B.Green, M.T. Henzl, J.M. Hosea, R.A. McPherson, J. Sneddon, and M.D. Alexander, "Selective Recovery of Gold and Other Metals Ions from an Algal Biomass", Env. Sci Technol 20: 206-208 (1986b).
- Department of Energy. Applied Research, Development, Demonstration, Testing, and Evaluation Plan for Environmental Restoration and Waste Management. Draft Report. November 1989. (1989)
- Failla, M.L., and E.D. Weinberg, "Cyclic Accumulation of Zinc by Candida utilis during Growth in Batch Culture", J. Gen. Microbiol 99: 85-97 (1977).

- Fisher, N.S., P. Bjerregaard, and S.W. Fowler, "Interactions of Marine Plankton with Transuranic Elements. 1. Biokinetics of Neptunium, Plutonium, Americium, and Californium in Phytoplankton", Limnol. Oceanogr. 28: 432-447 (1983).
- Gadd, G.M., "Accumulation of Metals by Microorganisms and Algae", in K.-J. Rhem (ed.), Biotechnology Handbook, Vol. 6B. Special Microbial Processes, VCH Verlagsgesellschaft: Weinheim, (1989, in press).
- Gekeler, W., E. Grill, E. L. Winnacker, and M. H. Zenk. "Algae Sequester Heavy Metals via Synthesis of Phytochelatin Complexes", Arch. Microbiol. 150:197-202 (1988).
- Greene, B., M.T. Henzl, J. M. Hosea, and D.W. Darnall, "Elimination of Bicarbonate Interference in the Binding of U(VI) in Mill-Waters to Freeze Dried Chlorella vulgaris", Biotech. Bioeng. 28:764-767 (1986).
- Hart, B.A., and B.D. Scaife, "Toxicity and Bioaccumulation of Cadmium in Chlorella pyrenoidosa", Environ. Res. 14: 401-413 (1977).
- Hart, B.A., P.E. Bertram, and B.D. Scaife, "Cadmium Transport by Chlorella pyrenoidosa", Environ. Res. 18: 327 (1979).
- Harvey, R.S., and R. Patrick, "Concentration of Cs, Zn, and Sr by Fresh-Water Algae", Biotech. Bioeng. 9: 449-456 (1967).
- Hassett, J.M, J.C. Jennett, and J.E. Smith, "Microplate Technique for Determining Accumulation of Metals of Algae", Appl. Environm. Microbiol. 41:1097-1106 (1981).
- Horikoshi, T., A. Nakajima, and T. Sakaguchi. "Uptake of Uranium by Various Cell Fractions of Chlorella regularis", Radioisotopes, 28: 9-12 (1979).
- Kuyucak, N., "Feasibility of Biosorbents Application", in Volesky, B., Editor, Biosorption of Heavy Metals, 4.3: 372-377, CRC Press Inc., Boca Raton, Florida (1990).
- Kuyucak, N. and Volesky, B., "Biosorbents for Removal and Recovery of Metals from Industrial Solutions", Biotech. Let. 10:137-142 (1988).
- Les, A., and R.W. Walker, "Toxicity and Binding of Copper, Zinc, and Cadmium by the Blue-green Alga Chroococcus parisi", Water Air, Soil Poll. 23: 129-139 (1984).
- Macaskie, L.E., and A.C.R. Dean, "Microbial Metabolism, Desolubilization, and Deposition of Heavy Metals: Metal Uptake by Immobilized Cells and Application ..." in Mizrahi, A. (ed.), Adv. Biotech. Processes, 12: in press (1989).
- Maeda, S., S. Nakashima, and T. Takeshita. "Bioaccumulation of Arsenic by Freshwater Algae and the Application to the Removal of Inorganic Arsenic from an Aqueous Phase. Part II. Chlorella vulgaris Isolated from Arsenic-Polluted Environment. Separation Sci. Technol. 20:153-161 (1985).

- Nakajima, A., T. Horikoshi, and T. Sakaguchi, "Studies on the Accumulation of Heavy Metal Elements in Biological Systems. XVII. Selective Accumulation of Heavy Metal Ions by Chlorella vulgaris", Eur. J. Appl. Microb. Biotech., 12:76 (1981).
- Olson, G.J., F.E. Brinckman, T.K. Trout, and D. Johnsonbaugh, "Bioaccumulation of Metals from Solution: New Technology for Recovery, Recycling and Processing", Int. Symp. Metallurgical Processes for the Year 2000, Las Vegas (1989).
- Polikarpov, G.G., Radioecology of Aquatic Organisms, Reinhold Publ. Co. N.Y. (1966).
- Sakaguchi, H., T. Tsuji, A. Nakajima, and T. Horikoshi, "Accumulation of Cadmium by Green Microalgae", Eur. J. Appl. Microb. Biotech. 8:207-215 (1979).
- Tarifeno-Silva, E. L., Y. Kawasaki, D. P. Yu, M. S. Gordon, and D. J. Chapman. "Aquacultural Approaches to Recycling of Dissolved Nutrients in Secondarily Treated Domestic Wastewaters - III. Uptake of Dissolved Heavy Metals by Artificial Food Chains", Wat. Res. 16: 59-65 (1982).
- Tsezos, M. and B. Volesky, "Biosorption of Uranium and Thorium", Biotech. Bioeng., 23:583-604 (1981).
- Volesky, B., Editor, Biosorption of Heavy Metals, CRC Press Inc., Boca Raton, Florida (1990).
- Wilde, E.W., and J.R. Benemann, Use of L-Lake for Algaculture, Savannah River Laboratory, DPST-88-588 (1989).
- Xue, H. W. Stumm and L. Sigg. "The Binding of Heavy Metals to Algal Surfaces", Wat. Res. 22: 917-926 (1988).
- Zimnik, P.R., and J. Sneddon, "Binding and Removal of Aluminum Ions in Waters by an Algal Biomass", Analytical Letters 21:1383-1396 (1988).

**DATE
FILMED**

5/01/92