CONF-9206271-4

RECEIVED BY
[illegible]

SYNTHESIS AND PROCESSING OF NANOSTRUCTURED MATERIALS*

Richard W. Siegel [illegible]
Materials Science Division
Argonne National Laboratory
Argonne, IL 60439

ANL/MSD/CP--75657

DE93 006413

December 1992

The submitted manuscript has been authored by a contractor of the U.S. Government under contract No. W-31-109-ENG-38. Accordingly, the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or allow others to do so, for U.S. Government purposes.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

An INVITED tutorial lecture presented at the NATO Advanced Study Institute on Mechanical Properties and Deformation Behavior of Materials Having Ultra-Fine Microstructures, Vimeiro, Portugal, June 28-July 10, 1992; to be published in Mechanical Properties and Deformation Behavior of Materials Having Ultra-Fine Microstructures, M. A. Nastasi et al., eds. (Kluwer, Dordrecht, 1993) in press.

*Work supported by the U. S. Department of Energy, BES-Materials Sciences, under Contract W-31-109-Eng-38.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

22

SYNTHESIS AND PROCESSING OF NANOSTRUCTURED MATERIALS

RICHARD W. SIEGEL
Materials Science Division
Argonne National Laboratory
Argonne, Illinois 60439 USA

ABSTRACT. Significant and growing interest is being exhibited in the novel and enhanced properties of nanostructured materials. These materials, with their constituent phase or grain structures modulated on a length scale less than 100 nm, are artificially synthesized by a wide variety of physical, chemical, and mechanical methods. In this NATO Advanced Study Institute, where mechanical behavior is emphasized, nanostructured materials with modulation dimensionalities from one (multilayers) to three (nanophase materials) are mainly considered. No attempt is made in this review to cover in detail all of the diverse methods available for the synthesis of nanostructured materials. Rather, the basic principles involved in their synthesis are discussed in terms of the special properties sought using examples of particular synthesis and processing methodologies. Some examples of the property changes that can result from one of these methods, cluster assembly of nanophase materials, are presented.

1. Introduction

1.1. BACKGROUND

Interest has focused increasingly on a variety of synthetic nanostructured materials, with average grain or other structural domain sizes below 100 nm, during the past several years with the anticipation that their properties will be different from, and often superior to, those of conventional materials that have phase or grain structures on a coarser size scale [1]. This interest has been stimulated not only by the recent efforts and successes in synthesizing a variety of fascinating atom clusters, zero-dimensionality quantum-well structures, and one-dimensionally modulated multilayered materials with nanometer scale modulations, but also by the exciting potential for synthesizing three-dimensionally modulated, bulk nanophase materials via the assembly of clusters of atoms [2].

Nanophase materials are only one example of the broad new class of nanostructured materials artificially synthesized with microstructures modulated in zero to three dimensions on length scales less than 100 nm that it has become possible to create over the past few years. However, they have gained much attention owing to their considerable technological potential in both monolithic materials and device applications. The various types of nanostructured materials share three features: atomic domains (grains or phases) spatially confined to less than 100 nm, significant atom fractions associated with interfacial environments, and interactions between their constituent domains. Nanostructured materials thus include zero-dimensionality atom clusters and cluster assemblies, one- and two-dimensionally modulated multilayers and overlayers, respectively, and their three-dimensional analogues, nanophase materials, as indicated schematically in Fig. 1.

The interest in the possibilities for nanostructuring materials has resulted in a variety of new methodologies for synthesizing materials with ultrafine structural or phase domains by means of which the creation of new levels of property engineering may become possible through the sophisticated control of scale, morphology, interaction, and architecture.

Figure 1. Schematic of the four types of nanostructured materials, classified according to integral modulation dimensionality: zero - clusters of any aspect ratio from 1 to ∞ ; one - multilayers; two - ultrafine-grained overlayers or buried layers; three - nanophase materials. Intermediate dimensionalities can exist.

For example, atom clusters in the nanometer size regime, containing hundreds to tens of thousands of atoms, can now be produced in sufficient numbers by means of either physical or chemical processes that they can be assembled into materials that can be studied by a variety of conventional experimental methods. These materials can take advantage of and incorporate a number of size-related effects in condensed matter ranging from electronic effects (so-called "quantum size effects") caused by spatial confinement of delocalized valence electrons and altered cooperative ("many body") atom phenomena, such as lattice vibrations or melting, to the suppression of such lattice-defect mechanisms as dislocation generation and migration in confined grain sizes. The possibilities to assemble size-selected atom clusters into new materials with unique or improved properties may thus impact our ability to engineer a wide variety of controlled optical, electronic, mechanical, and chemical properties with attendant useful technological applications.

The present paper focuses on the general principles that underlie the synthesis and processing of nanostructured materials. The special opportunities presented by our ability to create nanophase materials assembled from atom clusters of metals and ceramics synthesized by means of the gas-condensation method [3-7] are highlighted in terms of some of the property changes that nanostructuring can achieve. This method appears to be the most generally applicable of the presently available avenues for producing size-selected

atom clusters in the less-than-100-nm (nanostructure) regime, and thus appears to have very broad technological potential in the area of advanced materials. However, other approaches based on chemical or mechanical methodologies can frequently result in nanostructured material with similar property changes, albeit with rather less flexibility.

1.2. GENERAL PRINCIPLES

Generally, in synthesizing nanostructured materials from atomic or molecular precursors, one wants to be able to control a variety of microscopic aspects of the condensed ensemble. First, and probably foremost, is the size and size distribution of the constituent phases or structures. The desirable sizes are generally below 100 nm, since it is in this size range that various properties begin to change significantly owing to a variety of confinement effects. A property will be altered when the entity or mechanism (or combination thereof) responsible for that property is confined within a space smaller than some critical length associated with that entity or mechanism. So, for example, a metal which is conventionally ductile owing to the usual ease in creating and moving dislocations through its crystal lattice will become significantly harder when grain sizes are reduced to the point where dislocation sources are no longer able to operate at low levels of applied stress. Since the stress to operate a Frank-Read dislocation source is inversely proportional to the spacing between its pinning points, a critical length in this case is that for which the stress to operate this source becomes larger than the conventional yield stress for the given metal. Such confinement only appears to be different from that usually encountered in the technical literature, where for example the optical absorption properties of a so-called quantum-well semiconductor device are blue shifted (to shorter wavelengths) owing to the dimensions of the well becoming comparable to and smaller than the effective size of the excitonic state responsible for this absorption. The specifics are indeed quite different, but the underlying general principle of confinement is not.

Second, the composition of the constituent phases in a nanostructured material is of crucial importance, as it invariably is to the performance of conventional materials. This can simply mean maintaining phase purity during synthesis in a single phase nanostructured material, such as an oxide or a metal, or it can mean controlling the impurity doping levels, the stoichiometries, the solute gradients, the phase mixtures, or combinations of these in more complex nanostructured materials. In this case, however, the length scales over which such composition control must be maintained can push the limits of our technical capabilities.

The third aspect of nanostructured materials that one would like to be able to control in their synthesis is the nature of the interfaces created between constituent phases and, hence, the nature of the interactions across the interfaces. These interfaces can, of course, be grain boundaries between the same phase with differing orientations, heterophase interfaces, or free surfaces. Since the number of interfaces present in nanostructured materials is large compared with conventional materials, as shown in Fig. 2, this control can take on a much greater importance here. However, it is frequently rather difficult to create a nanostructured (or any other) material with prescribed interfaces. The greatest success to date has been achieved with one-dimensionally modulated nanoscale multilayers.

It is the interplay among these three features (domain size, composition, and interfaces) that determines the properties of nanostructured materials. In some cases, one or more of these features may dominate, as we will see in some of the examples given in Sec. 4. Thus, one wants to be able to build nanostructured materials under controlled conditions, but with an eye to the particular property or properties of interest. The degree of control available, of course, depends upon the particular synthesis method being used to create the given nanostructured material. Discussion of the very wide variety of synthesis and processing methods for the creation of nanostructured materials is well beyond the scope of

the present paper. Previous reviews [1, 8] can be usefully consulted for such information. In the present paper, some representative examples from the broad range of synthesis methods available for creating nanostructured materials will be considered, but emphasis is given here to one-dimensionally modulated multilayers produced by vapor deposition and three-dimensionally modulated nanophase materials assembled from gas-condensed atom clusters, since they can be used to illustrate many of the general principles just mentioned.

Figure 2. Percentage of atoms in grain boundaries (including grain boundary junctions) of a nanophase material as a function of grain diameter, assuming that the average grain boundary thickness ranges from 0.5 to 1.0 nm (ca. 2 to 4 atomic planes wide). From [9].

Before discussing specific methodologies for synthesizing nanostructured materials, it would be useful to first consider two examples of the manner in which material properties can be varied through the assembly of constituent domains through domain interaction effects. The first example relates to the optical absorption behavior of CdS clusters with diameters in the nanometer size regime made by any of a variety of methods, including chemical precipitation in solutions [10] or in zeolite supports [11]. This behavior is rather different from that for bulk CdS. The absorption edge is blue shifted to appreciably shorter wavelengths, owing to the effects of the quantum confinement discussed above. However, when these clusters are synthesized in zeolite supports with increasing loading, such that they become close enough to begin to interact through quantum tunneling, the absorption edge begins to shift back toward bulk behavior [12], as shown in Fig. 3. Hence, control of the average distance between clusters, even though they are not actually in contact, being separated by the cage structure of the zeolite, can enable control over a property of the assembled cluster ensemble. The second example is based upon a hypothetically simple multilayered nanostructure, an alternating set of uniform thickness Cu layers separated only by twist grain boundaries with twist axis normal to the layers and boundaries. Theoretical calculations [13] of the variation with decreasing multilayer modulation wavelength of the average lattice parameters and elastic constants of this chemically homogeneous Cu multilayer, shown in Fig. 4, demonstrate that even for such a simple case of layer-layer interaction, the effects on the elastic properties can be rather significant in the nanometer regime. One can therefore expect that in real nanostructured systems, where they can be synthesized, the effects of such domain interactions may be even more interesting.

Figure 3. Optical absorption spectra (a) for CdS clusters in the sodalite cages of zeolite Y for two different loadings compared to that for bulk CdS (μm size) [12]. (b) The cage structure of zeolite Y. From [11].

Figure 4. The average lattice parameters a and elastic constants (Young's modulus Y along the modulation direction z and shear modulus G parallel to the xy plane of the layer and boundaries) calculated as a function of modulation wavelength Λ for a simple Cu multilayer separated only by twist grain boundaries. From [13].

2. Synthesis

2.1. LAYER DEPOSITION

The deposition of layers of materials by means of electrolytic or vapor processes has had a long history and many different methods have been used for this over the years. Recently,

however, as the desire to lay down materials with greater control and precision has increased, a large number of new or improved synthesis methods have been developed. These include a variety of increasingly sophisticated single- or multi-bath systems for electrolytic deposition [14, 15] and an even broader and more sophisticated spectrum of chemical or physical vapor deposition methods [16, 17], which are capable of not only precise chemical and thickness control of the deposited layers on a nanometer scale, but also in some cases control of the nature of the interfaces between layers themselves. For the purposes of the present paper, it will be sufficient to show an example of the latter high degree of control now becoming available for the synthesis of nanostructured multilayers.

Figure 5. Schematic of a system for the synthesis of nanostructured ceramic multilayers by means of MOCVD (metal-organic chemical vapor deposition). After [18].

Figure 6. A cross-sectional high-resolution transmission electron micrograph of a nanostructured multilayer formed by alternating layers of TiO_2 (dark regions) and VO_2 (light regions). After [19].

Figure 5 shows a schematic diagram of a recently developed system [18] for the precise synthesis of ceramic multilayers by means of metal-organic chemical vapor deposition (MOCVD), a method that has been rather widely used in the synthesis of semiconductor

multilayers. The apparatus has four independently controlled metal-organic precursor feed lines, which avoid premixing of the reactants in the high-purity N_2 carrier gas, and a cold-wall horizontal growth chamber containing a substrate that can be maintained at temperatures up to 1000°C . The apparatus in Fig. 5 is quite flexible, since the synthesis variables (e.g., organometallic precursors, reactor pressure, gas flow rates, substrate material, temperature and orientation) can all be independently controlled to produce uniform ceramic multilayers with prescribed morphology, epitaxy, and stoichiometry. An example of the type of nanostructure that can be created by such a synthesis methodology is shown in Fig. 6. The organometallic precursors titanium isopropoxide ($\text{Ti}(\text{OC}_3\text{H}_7)_4$) and vanadium triethoxide ($\text{VO}(\text{OC}_2\text{H}_5)_3$) were used, respectively, to produce alternating layers of TiO_2 and VO_2 in an epitaxial multilayer assembly on a sapphire ($\alpha\text{-Al}_2\text{O}_3$) substrate. High-purity nitrogen was used as the carrier gas for the precursors and oxygen was used as the oxidant to form the stoichiometric compounds. It can be seen in Fig. 6 that by careful control of the synthesis parameters, alternating ceramic layers with nanometer-scale thicknesses can be deposited with essentially perfect epitaxy. By selecting appropriate substrate orientations and growth temperatures, both the phases and growth planes of the individual layers can be readily controlled.

2.2. CLUSTER ASSEMBLY

2.2.1. Chemical Precipitation. One of the traditional methods for synthesizing ultrafine powders or colloidal suspensions has been chemical precipitation. A wide variety of these methods, including sol-gel synthesis [20, 21] and the inverse micelle method [10] for example, have been successfully applied to the synthesis of nanometer sized clusters with narrow size distributions. Some additional references to the variety of interesting methods available can be found elsewhere [1, 2, 22-26] and in the pages of these Proceedings. Invariably, in each of these chemical precipitation methods, the synthesized clusters are burdened by surface layers (often intentionally introduced to cap the clusters at a given size or to keep them from agglomerating and forming large pores) from the solutions in which they are formed. These surface layers create few, if any, problems in the study of isolated clusters. However, if the clusters are to be assembled into bulk solids, as those of interest in this NATO Institute on mechanical behavior, then the surface layers can become contaminants in the grain boundaries of the cluster-consolidated material, and processing and properties can be adversely affected. Such potential problems can be avoided in the gas-condensation method for synthesizing nanophase materials.

2.2.2. Gas-Condensation. The synthesis of ultrafine-grained materials by the in situ consolidation in vacuum of nanometer size gas-condensed ultrafine particles or atom clusters [4] was first applied to metals [5, 6]. By consolidating clusters in this manner, materials with a large fraction of their atoms in grain boundaries could be formed, as described in the paper by H. Gleiter in these Proceedings. This method was subsequently applied to the synthesis of nanophase ceramics [7, 27]. However, the study of the gas condensation of ultrafine particles or atom clusters has had a rather longer history stretching back to the formation and use of 'smokes', such as carbon or bismuth 'blacks', for a variety of applications [28]. Scientific research into the controlled production of ultrafine particles by means of the gas-condensation method has been more recent [29-32], but still preceded cluster assembly and therefore provided an important basis for this work. In addition, of course, the previous knowledge of powder metallurgy and ceramics generated over an even longer period, provided much needed background information for the work on nanophase materials to progress. The application of these ideas in recent years [8, 9, 33-35] to the synthesis of a variety of nanophase metals and ceramics has built upon this broad scientific and technological base.

As stated in Sec. 1.2, control of the size or sizes and morphologies of the phase domains or granular entities (e.g., clusters) being assembled is of primary importance in any of the methods for the synthesis of nanostructured materials. Beyond this, composition of the phases and cleanliness of the interfaces between phases or grains must be controlled as well. In bulk gas-condensed cluster-assembled nanophase materials, such control appears to be readily available. Before proceeding with a description of their synthesis, it is useful to list some of the unique advantages of the assembly of nanophase materials under controlled atmospheres from gas-condensed clusters; they are as follows [3]:

- (1) The <100 nm sizes of the atom clusters and their surface cleanliness allow conventional restrictions of phase equilibria and kinetics to be overcome during material synthesis and processing; this results from the combination of short diffusion distances, high driving forces, and uncontaminated surfaces and interfaces available with cluster 'building blocks'.
- (2) The large fraction of atoms residing in the grain boundaries and interfaces of these materials allow for interface atomic arrangements to constitute significant volume fractions of material, and thus novel materials properties may result from such 'defect' atomic environments.
- (3) The reduced size scale and large surface-to-volume ratios of the individual nanophase grains can be predetermined and can alter and enhance a variety of physical and chemical properties.
- (4) A wide range of materials can be produced in this manner, including metals and alloys, intermetallic compounds, ceramics, and semiconductors; such materials can be synthesized to contain crystalline, quasicrystalline, or amorphous structures.
- (5) The extensive possibilities for reacting, coating, and mixing in situ various types, sizes, and morphologies of clusters create significant future potential for the synthesis of a variety of new multicomponent composites with nanometer-sized microstructures and engineered properties that can be both multifunctional and hierarchical. The studies carried out to date, nevertheless, have concentrated on single-phase metals and oxide ceramics.

Figure 7. Conceptual model for cluster formation via gas condensation. After [30].

The basic aspects of the generation of atom clusters via gas condensation can be described using the conceptual model shown in Fig. 7. A precursor material, either an element or compound, is evaporated in a gas maintained at a low pressure, usually well

below one atmosphere. The evaporated atoms or molecules lose energy via collisions with the gas atoms or molecules and undergo a homogeneous condensation to form atom clusters in the highly supersaturated vicinity of the precursor source. In order to maintain small cluster sizes, by minimizing further atom or molecule accretion and cluster-cluster coalescence, the clusters once nucleated must be removed rapidly from the region of high supersaturation. Since the clusters are already entrained in the condensing gas, this is readily accomplished by setting up conditions for moving this gas. Such gas motion has generally been driven by natural convection under the combined action of gravity and the temperature difference between the precursor source and a cooled thermophoretic cluster collection surface. However, a forced gas flow can be used instead of natural convective flow, which should yield significant advantages in terms of both cluster size control and process efficiency.

It should be emphasized that there are only three fundamental rates, that function relative to one another, which essentially control the formation of the atom clusters in the gas-condensation process [3]. They are (1) the rate of supply of atoms to the region of supersaturation where condensation occurs, (2) the rate of energy removal from the hot atoms via the condensing medium, the gas, and (3) the rate of removal of the clusters once nucleated from the supersaturation region. Other factors can also affect the clusters finally collected, particularly those that result in significant cluster-cluster coalescence, but these three rates represent the core of the process. Accordingly, the smallest cluster sizes for a given precursor are obtained for a low evaporation rate and condensation in a low pressure of a light inert gas such as He. These conditions lead to a lower supersaturation of precursor atoms in the gas, slower removal of energy from the evaporated atoms (via the lighter gas atoms at lower pressure), and more rapid convective gas flow owing also to the lower gas pressure. The rapid gas flow is significant, since it guarantees a shorter dwell time of the gas-entrained condensed clusters in the supersaturated region in which, if they remained, they would grow further.

A typical apparatus [36] which uses such a process for the synthesis of nanophase materials via the in situ consolidation of gas-condensed clusters is shown schematically in Fig. 8. It consists of an ultrahigh-vacuum (UHV) system fitted with two resistively-heated evaporation sources (which operate in the manner of Fig. 7), a cluster collection device (liquid-nitrogen filled cold finger) and scraper assembly, and in situ compaction devices for consolidating the powders produced and collected in the chamber. Before making the powders, the UHV system is first evacuated by means of a turbomolecular pump to below 10^{-5} Pa and then back-filled with a controlled high-purity gas atmosphere at pressures of about a few hundred Pa. For producing metal powders this is usually an inert gas, such as He, but it can alternatively be a reactive gas or gas mixture if, for example, clusters of a ceramic compound are desired.

The clusters that are collected via thermophoresis on the surface of the cold finger form very open, fractal structures. They are held on the collector surface rather weakly, via Van der Waals type forces, and are easily removed from this collection surface by means of a Teflon scraper. Upon removal, the clusters fall like 'snow' from the surface and are funneled into a set of compaction devices (see Fig. 8) capable of consolidation pressures up to about 1-2 GPa, in which the nanophase samples are formed at room temperature, or at elevated temperatures if needed. The pellets formed in this conventional research apparatus are typically about 9 mm in diameter and 0.2 to 1.0 mm thick, depending upon the amount of material made (usually a few hundred milligrams) and the experiments to be performed. The sizes of these samples have been more a matter of laboratory convenience than any real limitation of the gas-condensation method itself. All of the fundamental rates involved in the cluster synthesis can be significantly increased above those presently in use in the laboratory and scaled up production rates leading to samples with greatly increased sizes are clearly feasible. The scraping and consolidation are performed under UHV conditions

after removal of the inert or reactive gases from the chamber, in order to maximize the cleanliness of the particle surfaces and the interfaces that are subsequently formed. Also, any possibility of trapping remnants of these gases in the nanophase compact is minimized by consolidation in vacuum. It should be noted in this regard that the total surface area of the nanophase powders produced in a given run is so great that, for a residual gas pressure of less than 10^{-5} Pa in a volume the size of the UHV chamber used, little gas contamination of the cluster surfaces would be expected.

Figure 8. Schematic drawing of a gas-condensation chamber for the synthesis of nanophase materials. Precursor material evaporated from sources A and/or B condenses in the gas and is transported via convection to the liquid-nitrogen filled cold finger. The clusters are then scraped from the cold finger, collected via the funnel, and consolidated first in the low-pressure compaction unit and then in the high-pressure compaction unit, all in vacuum. From [36].

An example of a rather typical grain size distribution, here in as-consolidated TiO_2 , is shown in Fig. 9. It is quite narrow and has the log-normal shape typical of clusters formed via gas-condensation [30]; it is thus essentially identical to that for the clusters from which the nanophase sample was assembled. Indeed, this shape is rather typical for the grain size distribution in any of the nanophase materials thus far produced by the gas-condensation method. The asymmetric tail of the distribution extending to larger sizes is a manifestation of cluster-cluster coalescence in the gas-condensation process.

Figure 9. Grain size distribution for a nanophase TiO_2 (rutile) sample compacted to 1.4 GPa at room temperature, as determined by dark-field transmission electron microscopy. From [27].

Since the as-collected gas-condensed clusters are generally aggregated in rather open fractal arrays [29, 31], their consolidation at pressures of 1-2 GPa is easily accomplished, even at room temperature. The difficulties in consolidating the hard equiaxed agglomerates of fine powders resulting from conventional wet chemistry synthesis routes are mostly avoided. The sample densities resulting from cluster consolidation at room temperature have ranged up to about 97% of theoretical for nanophase metals and up to about 75-85% of theoretical for nanophase oxide ceramics. This "green-state" porosity represents (at least in part) a manifestation of powder agglomeration leading to void-like flaws. Fortunately, these appear to be capable of being removed by means of cluster consolidation at elevated temperatures and pressures without significant attendant grain growth.

If an elemental precursor is evaporated in an inert gas atmosphere, then the atom clusters formed and collected are the same material, only in a reconstituted form. However, if clusters of a compound, such as a ceramic oxide are desired, the synthesis process can become somewhat more complex. For example, in order to produce nanophase TiO_2 with a rutile structure and the grain size distribution shown in Fig. 9, Ti metal clusters condensed in He were first collected on the cold finger and subsequently oxidized by the introduction of oxygen into the chamber [27]. A similar method has been used to produce $\alpha\text{-Al}_2\text{O}_3$ [35] with an 18 nm average grain size after oxidizing Al clusters in air at 1000°C. If the vapor pressure of a compound is sufficiently large, as in the cases of MgO and ZnO, for example, it is possible to sublime the material directly from the oxide precursor in a He atmosphere containing, in addition, a partial pressure of O_2 to attempt to maintain oxygen stoichiometry during cluster synthesis. Such a method has been used [35] to produce such nanophase oxides with average grain sizes down to about 5 nm. Frequently, however, oxygen stoichiometry is not maintained.

In the case of nanophase TiO_2 cited above [27], the oxygen deficiency, while still present, is rather small and easily remedied as a result of the small grain sizes and short diffusion distances involved. Raman spectroscopy has been a useful tool in studying the oxidation state of nanophase TiO_2 owing to the intense and well studied Raman bands in both the anatase and rutile forms of this oxide and the observation that these bands were affected in nanophase samples [37]. A series of Raman spectra from two as-consolidated titanium dioxide nanophase samples and from one of these samples annealed in air until

fully oxidized to TiO_2 is shown in Fig. 10. The band broadening observed in the nanophase samples (and also band shifting in both the anatase and rutile phases) was confirmed [38] to be the result of an oxygen deficiency which could be subsequently removed in these samples by annealing in air. A subsequent calibration of this deviation from stoichiometry [39], shown in Fig. 11, indicated that the material produced in the apparatus of Fig. 8 was actually $\text{TiO}_{1.89}$. However, it could be easily oxidized to fully stoichiometric TiO_2 , if desired, without sacrificing its small grain size (12 nm). Also, if intermediate deviations from stoichiometry were sought, in order to optimize particular material properties sensitive to the presence of oxygen deficient defects, they could be readily accessed as well.

Figure 10. Raman spectra of two areas (a) and (b) of an as-compacted nanophase TiO_2 sample compared with spectra for area (b) after successive annealing in air for 0.5 h at 300°C (c), 500°C (d), 700°C (e), and 1000°C (f) (* indicates anatase $k=0$ phonons; + indicates rutile $k=0$ phonons). From [37].

Figure 11. Variation with O/Ti ratio of the peak position of (a) the rutile "447 cm^{-1} " vibrational mode and (b) the anatase "143 cm^{-1} " vibrational mode, as well as (c) this anatase mode's full width at half maximum (FWHM). From [39].

Most of the atom clusters assembled into nanophase materials to date have been generated from Joule-heated evaporation sources. However, such sources have limitations that need not be suffered, since a wide variety of other sources are also available. The primary limitations are source-precursor incompatibility, temperature range, uniformity and control, and dissimilar evaporation rates for different constituents in an alloy or compound precursor. Each of these limitations can be avoided by a host of alternative sources that have been developed over the years of ultrafine particle research [32], but which are only

now beginning to enter the field of nanophase materials synthesis. Among other sources for bringing atom supersaturations into a condensing gas medium that have been successfully used to produce clusters or ultrafine particles are Joule-heated ovens [40-42], sputtering [43-47], electron-beam heating [48-51], laser ablation [52], and plasma methods [53, 54]. It should be clear that this wide variety of evaporation methods will allow for greatly increased flexibility in the use of refractory or reactive precursors for clusters and will be especially useful as one moves toward synthesizing technological quantities of more complex multicomponent or composite nanophase materials in the future.

2.3. MECHANICAL ATTRITION

Mechanical attrition produces its nanostructures, not by cluster assembly, but by means of the structural decomposition of coarser-grained structures induced by severe mechanical deformation. Nanometer size grains nucleate within the shear bands of heavily deformed materials converting a coarse-grained structure to nanophase. The heavy deformation is usually induced by means of high-energy ball milling [55-57], but can result as well from surface wear phenomena [58] and other methods for introducing high densities of deformation, such as the high-energy shear process described by R. Valiev in these Proceedings. Thus, the individual grains are never isolated clusters and much synthesis and processing flexibility is lost. Nevertheless, ultrafine grain sizes can be readily accessed by this rather straightforward (brute-force) method, albeit with probable contamination from the sources of mechanical work. However, the method is already capable of producing commercial quantities of material, and for those applications in which careful control of purity or grain morphology are not important, and for which the desired properties are indeed accessible in the mechanically attrited nanostructures, it can be a useful source of these materials. The variation with grain size as a function of ball-milling time in Pd [59] is shown in Fig. 12(a). This behavior is found to be typical for ball milled metals and clearly shows that grain sizes down into the nanometer regime can be accessed, although it is more easily accomplished in relatively harder materials, as indicated by the relationship between minimum grain size and bulk modulus shown in Fig. 12(b). Mechanical attrition exercised at low temperatures ("cryomilling") can extend the range of applicability, as shown by Luton et al. [60] in their work on dispersion-strengthened Al.

Figure 12. (a) Average grain size, determined by X-ray line broadening, of Pd as a function of ball-milling time. (b) Minimum average grain size attained by ball milling various fcc metals plotted against their bulk modulus values. From [59].

3. Structure and Stability

Nanophase materials, as other nanostructured materials, are dominated by their ultrafine grain sizes and their large number of interfaces. In addition, however, other structural features such as pores and their associated free surfaces, grain boundary junctions, and other crystal lattice defects play a significant role in their properties. It has become increasingly clear that all of these aspects of the nature of nanophase materials must be considered in trying to fully understand these new materials [61].

3.1. GRAINS AND PORES

Our present knowledge of the grain structures of nanophase materials has resulted primarily from direct observations using transmission electron microscopy (TEM) [27, 62-64]. A typical high resolution image of a nanophase palladium sample is shown in Fig. 13. TEM has shown that the grains in nanophase compacts are rather equiaxed, similar to the atom clusters from which they were formed. The grains also appear to retain the narrow log-normal size distributions (Fig. 9) typical of the clusters formed in the gas-condensation method [30], since measurements of these distributions before or after cluster consolidation by dark-field electron microscopy yield rather similar results. On the other hand, the observations that the densities of nanophase materials consolidated from equiaxed clusters extend well beyond the theoretical limit (78%) for close packing of identical spheres indicate that an extrusion-like deformation of the clusters must result during the consolidation process, filling (at least partially) the pores among the grains. Observations by electron and X-ray scattering indicate, however, that no apparent preferred orientation or "texture" of the grains results from their uniaxial consolidation and that the grains in the nanophase compact are essentially randomly oriented with respect to one another.

Figure 13. High resolution transmission electron micrograph of a typical area in cluster-consolidated nanophase palladium. From [63].

Taken together, these various observations indicate that cluster extrusion in forming nanophase grains may result from a combination of deformation and diffusion processes. Such processes are also evident from recent scanning tunneling microscopy observations [65] on nanophase Pd and Ag. An example from Ag is shown in Fig. 14.

Figure 14. Scanning tunneling micrograph of nanophase silver. From [65].

All of the nanophase materials consolidated at room temperature to date have invariably possessed a degree of porosity ranging from about 25% to less than 5%, as measured by Archimedes densitometry, with the larger values for ceramics and the smaller ones for metals. Evidence for this porosity was first obtained by positron annihilation spectroscopy (PAS) [27, 66, 67] and more recently by precise densitometry [68] and porosimetry [69, 70] measurements. PAS is primarily sensitive to small pores [71], ranging from single vacant lattice sites to larger voids, but can probe these structures enclosed in the bulk of the material. Porosimetry measurements using the BET (Brunauer-Emmett-Teller) N_2 adsorption method [72], on the other hand, probe only pore structures open to the free surface of the sample, but can yield pore size distributions, which are unavailable from PAS. Densitometry using an Archimedes method, of course, integrates over all densities in the sample, including grains, pores (open or closed), and density decrements at defect sites. These measurements have together shown that the porosity in as-consolidated nanophase metals and ceramics is primarily in the less than 100 nm size regime (although some larger porous flaws have been observed), and usually of comparable sizes to the grains, but that the porosity is to a great extent interconnected and intersects with the specimen surfaces, as seen in Fig. 14. Fortunately, consolidation at elevated temperatures can remove this porosity without sacrificing the ultrafine grain sizes in these materials.

3.2. GRAIN BOUNDARIES

Owing to their ultrafine grain sizes, nanophase materials have a significant fraction of their atoms in grain boundary environments, where they occupy positions relaxed from their normal lattice sites. For conventional high-angle grain boundaries, these relaxations extend over about two atom planes on either side of the boundary, with the greatest relaxation existing in the first plane [13]. The significance of these atomic relaxations in nanophase materials can be better appreciated by the simple estimate of the fraction of atoms in grain

boundary environments as a function of grain size shown in Fig. 2. It can be seen that in the average grain diameter range between 5 and 10 nm, where much of the research on nanophase materials has focussed, grain boundary atom percentages range between about 15 and 50%. Since such a large fraction of their atoms reside in the grain boundaries of nanophase materials, it is clear that the interface structures can play a significant role in affecting the properties of these materials.

A number of early investigations on nanocrystalline metals, including X-ray diffraction [73], Mössbauer spectroscopy [74], positron lifetime studies [66, 67], and extended X-ray absorption fine structure (EXAFS) measurements [75, 76], were interpreted in terms of grain boundary atomic structures that may be random, rather than possessing either the short-range or long-range order normally found in the grain boundaries of conventional coarser-grained polycrystalline materials. This randomness was variously associated [33] with either the local structure of individual boundaries (as seen by a local probe such as EXAFS or Mössbauer spectroscopy) or the structural coordination among boundaries (as might be seen by X-ray diffraction). However, recent high resolution electron microscopy (HREM) investigations [62, 63] have indicated that their structures are rather similar to those of conventional high-angle grain boundaries. An extensive review of these results has recently appeared elsewhere [61].

The direct imaging of grain boundaries with HREM can avoid the complications that may arise from porosity and other defects in the interpretation of data from less direct methods, such as X-ray scattering and Mössbauer spectroscopy. Typical grain boundaries in nanophase palladium are shown in Fig. 13. A HREM study [62, 63], which included both experimental observations and complementary image simulations, indicated no manifestations of grain boundary structures with random displacements of the type or extent suggested by earlier X-ray studies on nanophase Fe, Pd, and Cu [73, 75, 76]. Contrast features at the observed grain boundaries that might be associated with disorder did not appear wider than 0.4 nm, indicating that any significant structural disorder which may be present essentially extends no further than the planes immediately adjacent to the boundary plane. Such localized lattice relaxation features are typical of high-angle grain boundary structures found in coarse-grained metals. HREM investigations of grain boundaries in nanophase Cu [58] and Fe alloys [77] produced by surface wear and high-energy ball milling, respectively, appear to support this view. The HREM image simulations [62, 63] for Pd indicated that average random atomic displacements of $\geq 12\%$ of a nearest neighbor distance, if present, could be readily observable by HREM for the assumed contrast conditions, which were identical to those used experimentally.

Indeed, as shown in Fig. 13 and in similar electron micrographs, the nanophase grain boundaries appear to be rather low energy configurations exhibiting flat facets interspersed with steps. Such structures could only arise if sufficient local atomic motion occurred during the cluster consolidation process to allow the system to reach at least a local energy minimum. Such observations suggest at least two conclusions [78]: first, that the atoms that constitute the grain boundary volume in nanophase materials have sufficient mobility during cluster consolidation to accommodate themselves into relatively low energy grain boundary configurations; and second, that the local driving forces for grain growth are relatively small, despite the large amount of energy stored in the many grain boundaries in these materials. These conclusions also have an impact upon the inherent grain size stability of nanophase materials described in Sec. 3.3.

The foregoing discussion suggests [78] that nanophase materials should be a valuable resource for studying the average properties of grain boundaries. The high number density of such defects in these materials enhance their influence on macroscopic properties, allowing these effects to be studied by a variety of experimental techniques. Indeed, a number of the effects observed in nanophase materials to date that have been deemed unusual may simply result from so many grain boundaries being available for study in a

sample for the first time. As pointed out in these Proceedings by H. Gleiter, for example, a wide range of investigations on nanophase grain boundaries indicate that one is seeing the effects from the wide distribution of interatomic spacings in the boundary structures. Since this behavior is generally expected from theoretical models of conventional high-angle grain boundaries [13, 79, 80], it remains to be seen whether there are any unexpected structural relaxations present in nanophase boundaries. For careful investigations of grain boundary properties to be successful in the future, however, specimen porosity will need to be removed, via consolidation at elevated temperature and/or pressure, so that its property contributions can be eliminated. By varying their grain size, the effects from interfaces and junctions in nanophase materials could be effectively separated in such future studies.

3.3. STABILITY

The ultrafine grain sizes of nanophase materials immediately raise a question regarding their relative stability against spontaneous grain growth. With so many grain boundaries present in these materials, and their concomitantly large stored interface energy, this question of stability against grain growth becomes important to address from both scientific and technological viewpoints. Interestingly, nanophase materials assembled from atomic clusters appear to possess an inherent grain size stability. Their grain sizes remain rather deeply metastable to elevated temperatures. For example, it has been found for nanophase TiO_2 [27] that the 12 nm initial average grain diameter for the grain size distribution shown in Fig. 9 changes very little with annealing to elevated temperatures, until about 0.4-0.5 of the absolute melting temperature of TiO_2 is reached. This behavior appears to be typical for the nanophase oxides already investigated [35] and for nanophase metals as well [81], as shown in the Arrhenius plot in Fig. 15. In the case of the TiO_2 , rapid grain growth only develops above the temperature at which the mean bulk diffusion distance $(D_{\text{Ti}})^{1/2}$ of Ti, the slower moving element in this compound, becomes comparable to the mean grain size, at which temperature any local barriers to grain growth would cease to be significant.

Figure 15. Arrhenius plot of the variation of average grain size, measured by dark-field transmission electron microscopy, with sintering temperature for nanophase Fe [81], TiO_2 [27], MgO/WO_x [35], and ZnO [35]. The oxide samples were annealed for 0.5 h in air at each temperature; the iron for 10 h in vacuum. From [82].

The observations of narrow grain size distributions, essentially equiaxed grain morphologies, and low energy grain boundary structures in nanophase materials suggest that the inherent resistance to grain growth observed for cluster-assembled nanophase materials results primarily from a sort of frustration [82]. It appears that the narrow grain size distributions normally observed in these cluster-assembled materials coupled with their relatively flat grain boundary configurations (and also enhanced by their multiplicity of grain boundary junctions) place these nanophase structures in a local minimum in energy from which they are not easily extricated. There are normally no really large grains to grow at the expense of small ones through an Ostwald ripening process, and the local grain boundaries, being essentially flat, have no curvature to tell them in which direction to migrate. Their stability thus appears to be analogous to that of a variety of closed-cell foam structures with narrow cell size distributions, which are stable (really, deeply metastable) despite their large stored surface energy. Under such conditions, only at temperatures above which bulk diffusion distances are comparable to or greater than the grain size and communication among grains becomes possible, as in the case of nanophase TiO_2 cited above, will this metastability give way to global energy minimization via rapid grain growth. Such a picture now appears to have some theoretical support [83]. However, it has also been recently suggested [84] that the porosity present in nanophase ceramics may assist in their stability against grain growth, as it does in conventional coarser-grained ceramics, and further support for such a stabilizing influence from voids in nanophase ceramics is presented by M. J. Mayo in these Proceedings. Nevertheless, the grain growth data for >96% dense nanophase TiAl intermetallic compound presented by C. Altstetter in these Proceedings indicate that grain boundary stabilization in nanophase intermetallics, at least, is not simply a result of the presence of significant porosity; these data also appear to be consistent with the frustration picture.

The diffusion controlled grain-growth behavior in nanophase materials is apparent in Fig. 15. The data in their high temperature limit fall, within their scatter, along straight lines in this Arrhenius plot. The effective activation energy of this high temperature limiting behavior is about $9 kT_m$ for all of the materials; it is thus approximately one half that for self-diffusion, or close to the value usually observed for normal grain boundary diffusion in polycrystalline materials. It should be pointed out that exceptions to this frustrated grain growth behavior would be expected if considerably broader grain size distributions were accidentally present in a sample, which would allow a few larger grains to grow at the expense of smaller ones, or if significant grain boundary contamination were present, allowing enhanced stabilization of the small grain sizes to further elevated temperatures. Occasional observations of each of these types of behavior have been made. One could, of course, intentionally stabilize against grain growth by appropriate doping by insoluble elements or composite formation in the grain boundaries. For these cluster assembled materials, such stabilization should be especially easy, since the grain boundaries are available as cluster surfaces prior to consolidation. The ability to retain the ultrafine grain sizes of nanophase materials is important when one considers the fact that it is their grain size and large number of grain boundaries that determine to a large extent their special properties. It might also be possible to further stabilize even pure single-phase nanophase materials against grain growth, if it were possible to control the precise nature of the grain boundaries formed. Unfortunately, at this time such control over the assembly of clusters via consolidation is not feasible, and essentially random ensembles of grains and high-angle grain boundaries result.

Another important aspect of stability in materials with reduced spatial dimensions in the nanometer size regime is phase stability. As one reduces the sizes of constituent phases sufficiently, equilibrium phase relations will change owing to expected changes in a variety of electronic and thermodynamic parameters of the confined atomic system. For example, it has long been known [85-87] that the melting temperature of small metal clusters is

suppressed well below that for the bulk solid, owing in part to a higher effective pressure in the confined system, an effect also recently demonstrated [88] for 2.4-7.6 nm diameter CdS semiconductor clusters synthesized by the inverse micelle chemical precipitation method [10]. The melting-point suppression can be rather dramatic, as shown in Fig. 16, where the smallest CdS clusters are seen to melt at about 1000 K below the bulk melting temperature. Related effects are also seen in cluster-consolidated materials. Investigation of nanophase Er oxides synthesized by the gas-condensation route showed [89] that new oxide phases related to previously observed high-pressure structures were formed in grains of about 10 nm diameter, even though the samples had never been exposed to sufficiently high external pressures. Similarly, it was recently reported [90] that nanophase (8 nm) yttria can be stabilized in its high-pressure polymorphic structure, γ -Y₂O₃. Thus, it seems clear that the effects of reduced spatial dimensions on phase stability need further investigation, since one cannot expect that the phase equilibria we know for conventional materials systems will apply in general to those of significantly reduced dimensions.

Figure 16. Size dependence of the melting temperature of CdS clusters determined by electron diffraction (■, +) and dark-field electron microscopy (▽). From [88].

4. Processing and Properties

Cluster-assembled nanophase materials, as do other nanostructured materials, possess a variety of properties that are considerably different and improved in comparison with those of conventional coarser-grained structures. These unique properties result from an interplay among the three fundamental features of their nature cited in Sec 1.2: atomic domains (e.g., grains) spatially confined to less than 100 nm, significant atom fractions associated with interfacial environments (e.g., grain boundaries or free surfaces), and interactions between their constituent domains. In some cases one of these features dominates, in other cases another feature does. Research on a variety of physical, chemical, and mechanical properties is beginning to yield a glimmer of understanding of just how this interplay manifests itself in the properties of these new materials. Several examples will be given from this particular class of nanostructured materials to try and give a sense of how the interplay among these aspects can significantly alter some useful technological properties of these materials.

First of all, the processing of nanophase materials is dramatically improved by the combination of ultrafine cluster (grain) sizes, short diffusion distances, and cleanliness of cluster surfaces prior to consolidation. For example, nanophase TiO_2 (rutile) exhibits significant improvements in both sinterability and resulting mechanical properties relative to conventionally synthesized coarser-grained rutile [27, 69, 91, 92]. Nanophase TiO_2 with a 12 nm initial mean grain diameter has been shown [27] to sinter under ambient pressures at up to 600°C lower temperatures than conventional coarser-grained rutile, as shown in Fig. 17, and without the need for any compacting or sintering aid, such as polyvinyl alcohol, which is usually required. Furthermore, it has more recently been demonstrated [69] that sintering the same nanophase material under pressure (1 GPa), or with appropriate dopants such as Y, can further reduce the sintering temperatures, while suppressing grain growth as well, thus allowing for the unique possibility to sinter nanophase ceramics to full density while retaining their ultrafine grain size. The resulting fracture characteristics [84, 91, 93] developed for sintered nanophase TiO_2 are as good, or in some aspects improved, relative to those for conventional coarser-grained rutile.

Figure 17. Vickers microhardness of TiO_2 (rutile) measured at room temperature as a function of 0.5 h sintering at successively increased temperatures. Results for a nanophase sample (filled squares) with an initial average grain size of 12 nm consolidated at 1.4 GPa are compared with those for coarser-grained samples with 1.3 μm initial average grain size sintered with (diamonds) or without (circles) the aid of polyvinyl alcohol from commercial powder consolidated at 0.1 GPa and 1.4 GPa, respectively. After [27].

Another property that is altered and can significantly affect the processing of nanostructured materials is diffusion. Atomic diffusion in nanophase materials, which can also have a significant bearing on their mechanical properties, such as creep and superplasticity, and electrical properties as well, has been found to be very rapid compared with conventional materials. Measurements of self- and solute-diffusion [91, 94-97] in as-consolidated nanophase metals (Cu, Pd) and ceramics (TiO_2) indicate that atomic transport is orders of magnitude faster in these materials than in coarser-grained polycrystalline samples. This very rapid diffusion in as-consolidated nanophase materials

appears to be intrinsically coupled with the porous nature of the interfaces in these materials, since the diffusion can be suppressed back to conventional values by sintering samples to full density, as shown by measurements of Hf diffusion in TiO_2 before and after densification by sintering [91]. Nonetheless, there exist considerable possibilities for efficiently doping nanophase materials at relatively low temperatures via the rapid diffusion available along their ubiquitous grain-boundary networks, with only short diffusion paths remaining into their grain interiors, to synthesize materials with tailored electrical, optical, or mechanical properties.

An example of the way in which the electrical response can be significantly altered by means of this low-temperature diffusion doping along the nanophase grain boundaries is shown in Fig. 18. Nanophase TiO_2 with a 12 nm grain size was doped at about the 1 atomic % level with Pt diffused in from the surface [35]. After annealing in air for 4 h at about 500°C , the ac conductivity of the sample was measured as a function of temperature [98]. The strongly nonlinear, and reversible, electrical response shown in Fig. 18, caused presumably by the Pt doping into the band gap of this wide band-gap (3.2 eV) semiconductor, suggests that the rather easy impurity doping of nanophase electroceramics via rapid diffusion down their many grain boundaries and interconnected pores may lead to a wide range of interesting device applications in the future. The enhanced low temperature sinterability of nanophase ceramics, without the need for any possibly contaminating additives, should help with device compatibility problems frequently encountered in such applications. However, much work remains to be done in this area.

Figure 18. The ac conductivity of Pt-doped nanophase TiO_2 as a function of temperature. The sample was pre-annealed in air at about 500°C for 4 h prior to the conductivity measurements; the electrical response is reversible with temperature.

Although the optical properties of colloidal or zeolite-supported size-selected clusters have been a popular subject for study [2, 10-12], rather limited research has been carried out so far on the optical properties of cluster-assembled nanophase materials. However there appear to be interesting prospects, based upon what has been accomplished for confined systems of atoms in which the sizes of constituent domains fall below the critical length scales pertinent to a given property. Figure 19 shows an example of how the ability to control the porosity in the synthesis of nanophase ceramics will apparently lead to some

rather interesting optical applications in the near future. It has been recently demonstrated [99] that the oxidation step in the synthesis of cluster-consolidated nanophase Y_2O_3 can be so controlled that the resulting "green-state" porosity of 25-35% has a size distribution sufficiently small and narrow, as shown in Fig. 19, that the as-consolidated material is effectively transparent. Samples of this material are shown in the inset of Fig. 19 along with a similar opaque sample containing a larger pore population. The ability to reduce the size of the porosity in such material to well below the wavelengths of visible or other radiation, coupled with the possibilities for efficient doping of these materials cited above, should lead to a variety of controllable optical properties and related applications.

Figure 19. Pore size distribution in nanophase Y_2O_3 compacted at room temperature under 500 Pa pressure to a density of between 65-75% of the theoretical value. A similar set of samples is shown in the inset along with an opaque sample with larger pores. After [99]

The chemical reactivity of nanophase materials can also be rather striking in comparison with that of conventional materials. Since the gas-condensed clusters, with their inherently high surface areas, are assembled via consolidation in the method described in Sec. 2.2.2, there can be an excellent degree of control over the total available surface area in these self-supported ensembles. Thus, one can maximize porosity for obtaining very high surface areas, remove most of it, but retain some to facilitate low-temperature doping or other processing, or fully densify the nanophase material. Also, as pointed out in Sec. 2.2.2, composition control can be readily achieved. Recently completed measurements [100] of the decomposition of H_2S over lightly consolidated, high surface area nanophase TiO_2 at 500°C demonstrate the enhanced chemical reactivity of nanophase materials rather well. Figure 20 shows the catalytic activity for S removal from H_2S via dissociative adsorption for nanophase TiO_2 (rutile) compared with that for other commercially available forms of TiO_2 with either the rutile or anatase structure. It can be seen that the nanophase sample was far more reactive than any of the other samples tested, both initially and also after extended exposure to the H_2S . This greatly enhanced activity was shown to result from a combination of unique and controllable features of the nanophase material, its high surface area combined with its rutile structure and its oxygen deficient composition.

Figure 20. Activity of nanophase TiO_2 for the dissociative adsorption of H_2S as a function of exposure time at 500°C compared with that from several commercially available TiO_2 materials and a reference (A: $76 \text{ m}^2/\text{g}$ nanophase rutile; B: $61 \text{ m}^2/\text{g}$ anatase; C: $2.4 \text{ m}^2/\text{g}$ rutile; D: $30 \text{ m}^2/\text{g}$ anatase; E: $20 \text{ m}^2/\text{g}$ rutile; F: reference alumina). From [100].

While there are considerably more extensive discussions of the mechanical behavior of nanostructured materials in the papers collected in these Proceedings, it is useful here to include a couple of examples to elucidate the relationships between these properties and the synthetic nanostructures in which they are manifest. The predominant mechanical property change resulting from reducing the grain sizes of nanophase metals is the significant increase in their strength [68, 101, 102]. Figure 21 shows recent microhardness results for several samples of nanophase Cu compared with results for a coarser-grained sample. The smallest grain size (6 nm) sample is seen to exhibit about a 500% increase in hardness over the coarser-grained (ca. $50 \mu\text{m}$) sample. Nanophase Pd samples with 5-10 nm grain sizes have also been observed to exhibit up to about a factor of five increase in hardness over coarser-grained (ca. $100 \mu\text{m}$) samples [101], with concomitant increases in their yield stress. The common strengthening behavior found in nanophase Cu and Pd indicates that this response is generic to nanophase metals, at least those with a fcc structure. The likelihood that such mechanical behavior is more broadly generic to nanophase metals in general is enhanced by the observations that nanophase metals and alloys produced via mechanical attrition also exhibit significantly enhanced strength. For example, Koch and coworkers [103, 104] have found hardness increases of factors of 4 to 5 in nanophase Fe and a factor of about 1.2 in nanophase Nb_3Sn when the grain size is reduced from 100 nm to 6 nm.

Figure 21. Vickers microhardness measurements at a number of positions across several nanophase Cu samples ranging in grain size from 6 to 50 nm, compared with similar measurements from an annealed conventional 50 μm grain size Cu sample. After [68].

The increased strength observed in ultrafine-grained nanophase metals, although apparently analogous to conventional Hall-Petch [105, 106] strengthening observed with decreasing grain size in coarser grained metals, must result from fundamentally different mechanisms. As discussed in Sec. 1.2, it is expected that as nanophase grain sizes decrease and fall below the critical length scale for a given mechanism to operate, the associated property will be significantly changed. The grain sizes in the nanophase metals (Cu, Pd) considered here are smaller than the necessary critical bowing lengths for Frank-Read dislocation sources to operate at the stresses involved and smaller also than the normal spacings between dislocations in a pile-up. Thus, adequate descriptions of the mechanisms responsible for the increased strength observed need to accommodate to the ultrafine grain-size scale in these materials. As this scale is reduced into the nanostructured regime, and conventional dislocation generation and migration become increasingly difficult, it is apparent that the energetic hierarchy of microscopic deformation mechanisms will become successively accessed. Thus, easier mechanisms (such as dislocation generation from Frank-Read sources) will become frozen out at sufficiently small grain sizes and more energetically costly mechanisms will become necessary to effect deformation. Hence, grain confinement appears to be the dominant cause for the increased strength of nanophase metals. Nevertheless, a contributing factor to the observed strengthening may also be the elastic strain accommodation [68] resulting from cluster consolidation.

Also in the area of mechanical behavior, but in a different class of materials, it has been observed from the earliest studies that nanophase ceramics are rather easily formed [27, 107-109]. Furthermore, recent nanoindenter measurements on nanophase TiO_2 [92] and ZnO [110] have demonstrated that a dramatic increase of strain rate sensitivity occurs with decreasing grain size, as shown in Fig. 22. Since this strong and similar grain-size dependence is found for sets of samples in which the porosity is changing very little (but for two materials with differing "green" densities: 75% for TiO_2 , 85% for ZnO), it appears that this increased tendency toward ductility is an intrinsic property of these ultrafine-grained ceramics. The strain rate sensitivity values measured at the smallest grain sizes yet investigated (12 nm in nanophase TiO_2 and 7 nm in ZnO) thus indicate ductile behavior of

these nanophase ceramics, as well as a significant potential for increased ductility at even smaller grain sizes and elevated temperatures. The maximum strain rate sensitivities measured in these studies, about 0.04, are already approximately one-quarter that for lead at room temperature, for example. However, no superplasticity has yet been observed in nanophase materials at room temperature, which would yield strain rate sensitivity values about an order of magnitude higher than the maximum observed. Nevertheless, it seems clear that at smaller grain sizes and/or at elevated temperatures, superplasticity of these materials should be observed. Indeed, some limited evidence for such behavior has recently appeared [109].

Figure 22. Strain rate sensitivity of nanophase TiO₂ [92] and ZnO [110] as a function of grain size. The strain rate sensitivity was measured by a nanoindentation method and the grain size was determined by dark-field transmission electron microscopy.

The enhanced strain rate sensitivity at room temperature found in the nanophase ceramics TiO₂ [92] and ZnO [110] shown in Fig. 22. appears to result from increased grain boundary sliding in this material, aided by the presence of porosity, ultrafine grain size, and probably rapid short-range diffusion as well. This behavior is therefore dominated by the presence of the numerous interfaces in these materials and the very short diffusion distances involved in effecting the necessary atomic healing of incipient cracks for grain boundary sliding to progress at the strain rates utilized without fracturing the sample. Extrapolating from this apparently generic behavior, one can expect that grain boundary sliding mechanisms, accompanied by short-range diffusion assisted healing events, would be expected to increasingly dominate the deformation of a wide range of nanophase materials. Enhanced forming and even superplasticity in a wide range of nanophase materials, including intermetallic compounds, ceramics, and semiconductors might become a reality. Consequently, increased opportunities for high deformation or superplastic near-net-shape forming of a very wide range of even conventionally rather brittle and difficult to form materials could result.

The possibilities for plastic forming nanophase ceramics to near-net shape appear to be well on their way to realization. Karch and Birringer [108] have recently demonstrated that nanophase TiO₂ could be readily formed to a desired shape with excellent detail below 900°C, and the fracture toughness was found to increase by a factor of two as well. The ability to extensively deform nanophase TiO₂ at elevated temperatures (ca. 800°C) without

cracking or fracture has been clearly demonstrated by Hahn and coworkers [109, 111]. While these latter demonstrations have been accompanied by significant grain growth in the samples at the elevated temperatures employed, it can be expected that lower temperature studies (below 0.4-0.5 of the absolute melting temperature) in the future will also allow for near-net-shape forming of nanophase ceramics with both their ultrafine grain sizes and their attendant properties retained.

5. Conclusions

The research accomplished to date indicates that there are tremendous opportunities for synthesizing nanostructured materials with new architectures at nanometer length scales from atomic or molecular precursors via the assembly of atom clusters and by a myriad of other techniques now becoming available. The keys to the future of nanostructured materials, however, will be both in our ability to significantly improve the properties of materials by artificially structuring them on these nanometer length scales and in developing the methods for producing these materials in commercially viable quantities. The future appears to hold great promise for nanostructured materials, based upon the limited knowledge that has already been accumulated, but much work remains to be done.

The examples presented in Sec. 4 have demonstrated that, even in our crude initial attempts to change and to control the properties of materials via nanostructuring, it is already possible to dramatically alter a variety of technologically important properties of materials in this manner. It was shown that the strength of normally very ductile pure metals can be increased by orders of magnitude simply by reducing their grain sizes into the range where dislocation generation and migration becomes confined and difficult. On the hand, normally very brittle oxide ceramics can be rendered more ductile and formable by reducing their grain sizes into the range where grain boundary sliding becomes facilitated by the high number density of internal interfaces and the rapid atomic diffusion therein. Since cluster "building blocks" can already be assembled with some modicum of control over the retained porosity and composition in the nanophase compact, it was also demonstrated that significant positive effects on the electrical response of a wide band-gap semiconductor 'device', the optical transparency of a nanophase ceramic 'window', and the chemical reactivity of a self-supported nanophase 'catalyst' can result. The possibilities for engineering the electrical, optical, and catalytic properties of nanostructured materials will clearly be further enhanced by the ability to further control the compositions and defect structures in these materials. Such examples suggest that even more exciting opportunities may be available as we learn to synthesize more sophisticated multifunctional composite nanostructured materials in the future.

Combining the various aspects of nanometer scale and composition and interface control in nanostructured materials to create a variety of new technological materials with atomically engineered properties will be a great challenge. Fortunately, we are beginning to learn something about the relationships between nanostructure and material properties and how these might be changed through a variety of synthesis and processing methodologies to control material performance. It seems quite possible that by developing the means for creating new materials engineered from atomic or molecular precursors that we may indeed be on the threshold of a new era in materials technology. It is a challenge, therefore, that appears to be well worth the effort.

ACKNOWLEDGEMENT. This work was supported by the U.S. Department of Energy, BES-Materials Sciences, under Contract W-31-109-Eng-38.

References

1. B. H. Kear, L. E. Cross, J. E. Keem, R. W. Siegel, F. Spaepen, K. C. Taylor, E. L. Thomas, and K.-N. Tu, **Research Opportunities for Materials with Ultrafine Microstructures** (National Academy, Washington, DC, 1989), Vol. NMAB-454.
2. R. P. Andres, R. S. Averbach, W. L. Brown, L. E. Brus, W. A. Goddard, III, A. Kaldor, S. G. Louie, M. Moskovits, P. S. Peercy, S. J. Riley, R. W. Siegel, F. Spaepen, and Y. Wang, *J. Mater. Res.* **4**, 704 (1989).
3. R. W. Siegel, in **Materials Science and Technology**, Vol. 15: Processing of Metals and Alloys, R. W. Cahn, ed. (VCH, Weinheim, 1991) p. 583.
4. H. Gleiter, in **Deformation of Polycrystals: Mechanisms and Microstructures**, N. Hansen et al., eds. (Risø National Laboratory, Roskilde, 1981) p. 15.
5. R. Birringer, H. Gleiter, H.-P. Klein, and P. Marquardt, *Phys. Lett.* **102A**, 365 (1984).
6. R. Birringer, U. Herr, and H. Gleiter, *Suppl. Trans. Jpn. Inst. Met.* **27**, 43 (1986).
7. R. W. Siegel and H. Hahn, in **Current Trends in the Physics of Materials**, M. Yussouff, ed. (World Scientific, Singapore, 1987) p. 403.
8. H. Gleiter, *Prog. Mater. Sci.* **33**, 223 (1989).
9. R. W. Siegel, *Ann. Rev. Mater. Sci.* **21**, 559 (1991).
10. M. L. Steigerwald and L. E. Brus, *Ann. Rev. Mater. Sci.* **19**, 471 (1991).
11. G. D. Stucky and J. E. Mac Dougall, *Science* **247**, 669 (1990).
12. N. Herron, Y. Wang, M. Eddy, G. Stucky, D. E. Cox, K. Moller, and T. Bein, *J. Amer. Chem. Soc.* **111**, 530 (1989).
13. D. Wolf and J. F. Lutsko, *Phys. Rev. Lett.* **60**, 1170 (1988).
14. L. M. Goldman, B. Blanpain, and F. Spaepen, *J. Appl. Phys.* **60**, 1374 (1986).
15. D. S. Lashmore, R. Oberle, M. P. Dariel, L. H. Bennett, and L. Swartzendruber, *Mater. Res. Soc. Symp. Proc.* **132**, 219 (1989).
16. B. W. Dodson, L. J. Schowalter, J. E. Cunningham, and F. E. Pollak, eds., *Mater. Res. Soc. Symp. Proc.* **160** (1989).
17. T. M. Bessmann and B. M. Gallois, eds., *Mater. Res. Soc. Symp. Proc.* **168** (1990).
18. H. L. M. Chang, J. C. Parker, H. You, J. J. Xu, and D. J. Lam, *Mater. Res. Soc. Symp. Proc.* **168**, 343 (1990).
19. H. L. M. Chang, Y. Gao, J. Guo, C. M. Foster, H. You, T. J. Zhang, and D. J. Lam, *J. de Phys. IV*, C2-953 (1991).
20. L. L. Hench and D. R. Ulrich, **Science of Chemical Processing** (Wiley, New York, 1986).
21. L. C. Klein, *Ann. Rev. Mater. Sci.* **15**, 227 (1985).
22. I. A. Aksay, G. L. McVay, and D. R. Ulrich, eds., **Processing Science of Advanced Ceramics**, *Mater. Res. Soc. Symp. Proc.* **155** (1989).
23. P. C. Rieke, P. D. Calvert, and M. Alper, eds., **Materials Synthesis Utilizing Biological Processes**, *Mater. Res. Soc. Symp. Proc.* **174** (1990).
24. R. S. Averbach, D. L. Nelson, and J. Bernholc, eds., **Clusters and Cluster-Assembled Materials**, *Mater. Res. Soc. Symp. Proc.* **206** (1991).
25. G. M. Whitesides, J. P. Mathias, and C. T. Seto, *Science* **254**, 1312 (1991).
26. A. H. Heuer, D. J. Fink, V. J. Laraia, J. L. Arias, P. D. Calvert, K. Kendall, G. L. Messing, J. Blackwell, P. C. Rieke, D. H. Thompson, A. P. Wheeler, A. Veis, and A. I. Caplan, *Science* **255**, 1098 (1992).

27. R. W. Siegel, S. Ramasamy, H. Hahn, Z. Li, T. Lu, and R. Gronsky, *J. Mater. Res.* **3**, 1367 (1988).
28. A. I. Pfund, *Rev. Sci. Instr.* **1**, 397 (1930).
29. K. Kimoto, Y. Kamiya, M. Nonoyama, and R. Uyeda, *Jpn. J. Appl. Phys.* **2**, 702 (1963).
30. C. G. Granqvist and R. A. Buhrman, *J. Appl. Phys.* **47**, 2200 (1976).
31. A. R. Thölen, *Acta Metall.* **27**, 1765 (1979).
32. R. Uyeda, *Prog. Mater. Sci.* **35**, 1 (1991).
33. R. Birringer and H. Gleiter, in *Encyclopedia of Materials Science and Engineering*, Suppl. Vol. 1, R. W. Cahn, ed. (Pergamon Press, Oxford, 1988) p. 339.
34. H. Hahn, J. A. Eastman, and R. W. Siegel, in *Ceramic Transactions, Ceramic Powder Science*, Vol. 1, Part B, G. L. Messing et al., eds. (American Ceramic Society, Westerville, 1988) p. 1115.
35. J. A. Eastman, Y. X. Liao, A. Narayanasamy, and R. W. Siegel, *Mater. Res. Soc. Symp. Proc.* **155**, 255 (1989).
36. R. W. Siegel and J. A. Eastman, *Mater. Res. Soc. Symp. Proc.* **132**, 3 (1989).
37. C. A. Melendres, A. Narayanasamy, V. A. Maroni, and R. W. Siegel, *J. Mater. Res.* **4**, 1246 (1989).
38. J. C. Parker and R. W. Siegel, *J. Mater. Res.* **5**, 1246 (1990).
39. J. C. Parker and R. W. Siegel, *Appl. Phys. Lett.* **57**, 943 (1990).
40. K. Sattler, J. Mühlbach, and E. Recknagel, *Phys. Rev. Lett.* **45**, 821 (1980).
41. K. Sattler, *Ultramicroscopy* **20**, 55 (1986).
42. K. Sattler, *Z. Phys. D* **3**, 223 (1986).
43. H. Oya, T. Ichihashi, and N. Wada, *Jpn. J. Appl. Phys.* **21**, 554 (1982).
44. S. Yatsuya, K. Yamauchi, T. Kamakura, A. Yanagada, H. Wakaiyama, and K. Mihama, *Surface Sci.* **156**, 1011 (1985).
45. S. Yatsuya, T. Kamakura, K. Yamauchi, and K. Mihama, *Jpn. J. Appl. Phys., Part 2*, **25**, L42 (1986).
46. H. Hahn and R. S. Averbach, *J. Appl. Phys.* **67**, 1113 (1990).
47. G. M. Chow, R. L. Holtz, A. Pattnaik, A. S. Edelstein, T. E. Schlesinger, and R. C. Cammerata, *Appl. Phys. Lett.* **56**, 1853 (1990).
48. S. Iwama, E. Shichi, and T. Sahashi, *Jpn. J. Appl. Phys.* **12**, 1531 (1973).
49. S. Iwama, K. Hayakawa, and T. Arizumi, *J. Cryst. Growth* **56**, 265 (1982); *ibid.* **66**, 189 (1984).
50. S. Iwama and K. Hayakawa, *Surface Sci.* **156**, 85 (1985).
51. B. Günther and A. Kumpmann, *Nanostructured Mater.* **1**, 27 (1992).
52. A. Matsunawa and S. Katayama, in *Laser Welding, Machining and Materials Processing*, Proc. ICALEO '85, C. Albright, ed. (IFS Publ. Ltd., 1985) p. 205.
53. K. Baba, N. Shohata, and M. Yonezawa, *Appl. Phys. Lett.* **54**, 2309 (1989).
54. M. Uda, *Nanostructured Mater.* **1**, 101 (1992).
55. E. Hellstern, H. J. Fecht, Z. Fu, and W. L. Johnson, *J. Appl. Phys.* **65**, 305 (1989).
56. C. C. Koch, J. S. C. Jang, and S. S. Gross, *J. Mater. Res.* **4**, 557 (1989).
57. H. J. Fecht, E. Hellstern, Z. Fu, and W. L. Johnson, *Adv. Powder Metall.* **1-2**, 111 (1989).
58. S. K. Ganapathi and D. A. Rigney, *Scripta Metall. et Mater.* **24**, 1675 (1990).
59. J. Eckert, J. C. Holzer, C. E. Krill, III, and W. L. Johnson, *J. Mater. Res.* **7**, 1751 (1992); *Mater. Res. Soc. Symp. Proc.* **238**, 745 (1992).
60. M. J. Luton, C. S. Janath, M. M. Disko, S. Matras, and J. Vallone, *Mater. Res. Soc. Symp. Proc.* **132**, 79 (1989).

61. R. W. Siegel, in **Materials Interfaces: Atomic-Level Structure and Properties**, D. Wolf and S. Yip, eds. (Chapman and Hall, London, 1992) p. 431.
62. G. J. Thomas, R. W. Siegel, and J. A. Eastman, *Mater. Res. Soc. Symp. Proc.* **153**, 13 (1989).
63. G. J. Thomas, R. W. Siegel, and J. A. Eastman, *Scripta Metall. et Mater.* **24**, 201 (1990).
64. W. Wunderlich, Y. Ishida, and R. Maurer, *Scripta Metall. et Mater.* **24**, 403 (1990).
65. K. Sattler, G. Raina, M. Ge, N. Venkateswaran, J. Xhie, Y. X. Liao, and R. W. Siegel, *J. Appl. Phys.*, to be published (1993).
66. H. E. Schaefer, R. Würschum, M. Scheytt, R. Birringer, and H. Gleiter, *Mater. Sci. Forum* **15-18**, 955 (1987).
67. H. E. Schaefer, R. Würschum, R. Birringer, and H. Gleiter, *Phys. Rev. B* **38**, 9545 (1988).
68. G. W. Nieman, J. R. Weertman, and R. W. Siegel, *J. Mater. Res.* **6**, 1012 (1991).
69. H. Hahn, J. Logas, and R. S. Averbach, *J. Mater. Res.* **5**, 609 (1990).
70. W. Wagner, R. S. Averbach, H. Hahn, W. Petry, and A. Wiedenmann, *J. Mater. Res.* **6**, 2193 (1991).
71. R. W. Siegel, *Ann. Rev. Mater. Sci.* **10**, 393 (1980).
72. S. J. Gregg and K. S. W. Sing, **Adsorption, Surface Area and Porosity** (Academic Press, New York, 1982).
73. X. Zhu, R. Birringer, U. Herr, and H. Gleiter, *Phys. Rev. B* **35**, 9085 (1987).
74. U. Herr, J. Jing, R. Birringer, U. Gonser, and H. Gleiter, *Appl. Phys. Lett.* **50**, 472 (1987).
75. T. Haubold, R. Birringer, B. Lengeler, and H. Gleiter, *J. Less-Common Metals* **145**, 557 (1988).
76. T. Haubold, R. Birringer, B. Lengeler, and H. Gleiter, *Phys. Lett. A* **135**, 461 (1989).
77. M. L. Trudeau, A. Van Neste, and R. Schultz, *Mater. Res. Soc. Symp. Proc.* **206**, 487 (1991).
78. R. W. Siegel and G. J. Thomas, *Ultramicroscopy* **40**, 376 (1992).
79. D. Wolf and J. F. Lutsko, *J. Mater. Res.* **4**, 1467 (1989).
80. S. R. Phillpot, D. Wolf, and S. Yip, *MRS Bulletin XV*(10), 38 (1990).
81. E. Hort, Diploma Thesis, Universität des Saarlandes, Saarbrücken (1986).
82. R. W. Siegel, *Mater. Res. Soc. Symp. Proc.* **196**, 59 (1990).
83. N. Rivier, in **Proc. NATO Intl. Symp. Physics and Chemistry of Finite Systems: from Clusters to Crystals**, P. Jena et al., eds. (Kluwer, Dordrecht, 1992) p. 189.
84. H. J. Höfler and R. S. Averbach, *Scripta Metall. et Mater.* **24**, 2401 (1990).
85. Ph. Buffat and J.-P. Borel, *Phys. Rev. A* **13**, 2287 (1976).
86. M. Y. Han and R. L. Whetten, *Phys. Rev. Lett.* **61**, 1190 (1988).
87. R. S. Berry, J. Jellinek, and G. Natanson, *Phys. Rev. A* **30**, 919 (1984).
88. A. N. Goldstein, C. M. Echer, and A. P. Alivisatos, *Science* **256**, 1425 (1992).
89. Z. Li, H. Hahn, and R. W. Siegel, *Mater. Lett.* **6**, 342 (1988).
90. G. Skandan, C. M. Foster, H. Frase, M. N. Ali, J. C. Parker, and H. Hahn, *Nanostructured Mater.* **1**, 313 (1992).
91. R. S. Averbach, H. Hahn, H. J. Höfler, J. L. Logas, and T. C. Chen, *Mater. Res. Soc. Symp. Proc.* **153**, 3 (1989).
92. M. J. Mayo, R. W. Siegel, A. Narayanasamy, and W. D. Nix, *J. Mater. Res.* **5**, 1073 (1990).
93. Z. Li, S. Ramasamy, H. Hahn, and R. W. Siegel, *Mater. Lett.* **6**, 195 (1988).
94. J. Horváth, R. Birringer, and H. Gleiter, *Solid State Commun.* **62**, 319 (1987).
95. J. Horváth, *Defect and Diffusion Forum* **66-69**, 207 (1989).

96. H. Hahn, H. Höfler, and R. S. Averbach, Defect and Diffusion Forum **66-69**, 549 (1989).
97. S. Schumacher, R. Birringer, R. Straub, and H. Gleiter, Acta Metall. **37**, 2485 (1989).
98. A. Narayanasamy, J. A. Eastman, R. W. Siegel, unpublished results.
99. G. Skandan, H. Hahn, and J. C. Parker, Scripta Metall. et Mater. **25**, 2389 (1991).
100. D. D. Beck and R. W. Siegel, J. Mater. Res. **7**, 2840 (1992).
101. G. W. Nieman, J. R. Weertman, and R. W. Siegel, Scripta Metall. **23**, 2013 (1989).
102. G. W. Nieman, J. R. Weertman, and R. W. Siegel, Scripta Metall. et Mater. **24**, 145 (1990).
103. J. S. C. Jang and C. C. Koch, Scripta Metall. et Mater. **24**, 1599 (1990).
104. C. C. Koch and Y. S. Cho, Nanostructured Mater. **1**, 207 (1992).
105. E. O. Hall, Proc. Phys. Soc. London B**64**, 747 (1951).
106. N. J. Petch, J. Iron Steel Inst. **174**, 25 (1953).
107. J. Karch, R. Birringer, and H. Gleiter, Nature **330**, 556 (1987).
108. J. Karch and R. Birringer, Ceramics International **16**, 291 (1990).
109. H. Hahn, J. Logas, H. J. Höfler, P. Kurath, and R. S. Averbach, Mater. Res. Soc. Symp. Proc. **196**, 71 (1990).
110. M. J. Mayo, R. W. Siegel, Y. X. Liao, and W. D. Nix, J. Mater. Res. **7**, 973 (1992).
111. M. Guermazi, H. J. Höfler, H. Hahn, and R. S. Averbach, J. Amer. Cer. Soc. **74**, 2672 (1991).

END

DATE
FILMED

5/04/93