Final Technical Report

(01 April 1989 - 31 March 1992)

Deterministic Analysis of Processes at Corroding Metal Surfaces and the Study of Electrochemical Noise in These Systems

Principal Investigator:

**Professor R.M. Latanision
Department of Materials Science and Engineering
Massachusetts Institute of Technology
Cambridge, MA 02139-4307
Phone: (617) 253-4697
Fax: (617) 253-8745**

**Grant No. DE-FG02-89ER 45388
DOE Scientific Officer: Dr. Joseph B. Darby**

June 1992

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Table of Contents	Page
Project Summary	i
1. Introduction	1
2. Results From Previous Work	3
2.1 Butler-Volmer Equation	3
2.2 The Model	7
2.3 Width Measurements	11
2.4 Site Statistics	16
2.5 Surface Morphology	23
2.6 Summary	26
3. Future Research	32
3.1 Approach	32
3.2 Morphological Aspects of Surface Kinetics	34
3.3 Simulation of Metal Dissolution	37
3.3.1 Surface Scaling and Phase Transitions	38
3.3.2 Site Dependent Activation Energies	40
3.4 Passivation	47
3.5 Dynamic Model of Dissolution Current	48
4. References	52
5. Publications	55

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Project Summary

Our recent studies show that microscopic analysis via computer simulations of electrochemically dissolving metal surfaces can lead to a fundamental understanding of the relationship between surface morphology and dissolution kinetics. Microscopic information on surface processes is not contained in phenomenological equations such as the Butler-Volmer equation, which is commonly used to describe electrode dissolution. In particular, we find that the surface roughness and, consequently, the number of active sites are determined by thermodynamic parameters such as the applied electrode potential. The morphology of surfaces has proved to be an essential aspect of kinetic processes such as crystal growth and mineral dissolution. Electrochemical processes, however, are fundamentally different in that they feature the presence of very high electrical fields at the interface, which directly affect the surface reactions. To date, treatments of the kinetics of electrochemically dissolving metal surfaces have ignored surface morphology.

We propose to continue investigating morphological aspects of electrode processes with further development of our computational models. An important step in our studies will bring existent experimental data into the simulation, such as activation energies for dissolution, in order to obtain kinetic results and to test the proposed dissolution mechanisms based on competition between bonding and applied electrical potential. We also intend to study the first steps of passivation phenomenon which are controlled by deposition of oxygen ions on the dissolving surface. Finally, our model will allow us to address fundamental origins of electrochemical noise. Despite of the large amount of published experimental data studying fluctuations in electrode potential and current, little work has been done in understanding this noise on a microscopic scale. We have shown that the dissolution process is accompanied by continuous fluctuations of the surface roughness. These fluctuations are naturally built into the context of the statistics of a dissolving surface and may be a fundamental source of noise.

1 - Introduction

The control of metal dissolution processes is important in fields ranging from battery technology to corrosion. Nevertheless, metal dissolution remains a poorly understood class of electrochemical reactions. Although the reaction sequence for dissolution of many metals have been elucidated, kinetic descriptions are based on area averaged values of parameters that describe the relationship between the rate of reaction and the activation energy. Theoretical and experimental research on metal dissolution has focused traditionally on macroscopic processes and features. However, in the last few years there has been considerable interest in examining these processes on a microscopic scale.

Problems encountered in metal dissolution and corrosion are common to other dissolution processes described by activated complex theory, including dissolution of semiconductors and minerals. There are a number of critical issues that are general to all dissolution reactions, including: (i) the role of surface active sites, dislocations, and other heterogeneities to the dissolution kinetics, and (ii) whether rate equations should be written in terms of the concentration of surface species, solution species, or both.

To date there has been little theoretical work related to metal dissolution on a microscopic scale, although there have been considerable reports of theoretical studies of etch pit formation and dissolution of semiconductors [1]. Very recently, changes in global climates has stimulated research into chemical dissolution of minerals by acid rain. Major contributions in this area have been based on theoretical modelling of the dissolution process on a microscopic scale [2-5]. This work illustrates that the problems encountered in metal dissolution and corrosion are common to a wide range of dissolution processes of technological importance.

This proposal describes a research program to continue our work on theoretical modelling of metal dissolution. Over the next few years, results from theoretical modelling of dissolution, in conjunction with new experimental techniques such as in situ scanning tunnelling microscopy, are expected to provide a new insight into the processes controlling metal dissolution and corrosion.

Preliminary work in this program has been concerned with the relationship between dissolution kinetics and surface structure (see Section 2). We plan to extend this work to consider important parameters related to surface structure and to explore theoretical models of kinetic processes supported by experimental data (see Section 3). In addition, we propose to use the procedures developed during this phase of the work to address the issue of factors controlling passivation processes on a microscopic scale.

The technological significance of this work is particularly important with respect to a microscopic understanding of corrosion and passivation processes. A number of fundamental issues related to metal corrosion have not been resolved since Wagner and Traud [6] first proposed a phenomenological description of the relationship between anodic and cathodic processes during corrosion processes. This work will address issues such as:

- (i) the role of surface sites with low coordination numbers, and
- (ii) the dimensions and time constant of anodic areas during corrosion.

Analysis of dissolution processes on a microscopic scale will also allow us to address the issue of fluctuations in these systems. The Butler-Volmer equation, derived from activated complex theory, for example, expresses the relationship between the mean rate of reaction and the activation energy as a function of electrode potential and concentration terms. On a microscopic scale, the stochastic nature of dissolution processes gives rise to fluctuations in the dissolution current (or potential) that cannot be described by the Butler-Volmer equation. The study of fluctuations in electrochemical systems has gained considerable interest since it should contain information on the kinetic processes occurring at the interface. Fluctuations in current, or potential, have been used to analyze corrosion rates [7-9] and to investigate events leading to breakdown of passive films [10-16]. In semiconductor/electrolyte systems, it is also well established that kinetic information is contained in fluctuations in the current [17-18]. Fundamental sources of this measurable electrochemical noise are, however, poorly understood. The work to be done under this proposal may provide the first tools for establishing statistical mechanisms with which fluctuations are inherently built in these systems.

2 - Results From Previous Work

2.1 Butler-Volmer Equation

Morphological changes of the electrode surface undergoing electrochemical processes are of central interest to this research. For example, we wish to determine the relationship between reaction site specificities and local morphology. Further, evolution of the surface would then determine the localization and dynamics of anodic and cathodic sites. Our first studies focused on the evolution of surface morphology during electrochemical dissolution under an applied electrical field. Under open circuit conditions, the dissolution reaction is accompanied by some cathodic reaction at the same surface, which constitutes the reduction of cationic species originally in solution. By anodically polarizing the interface, we reduce the cathodic reaction to negligible values and restrict our analysis to the simpler case of dissolution of atomic species from the surface into the electrolyte.

Electrode kinetics have been extensively studied using phenomenological treatments that predict expressions for mean values of parameters such as rates of reactions. The Butler-Volmer equation is such an expression:

$$i = i_0 \{ \exp[\alpha n F \eta / RT] - \exp[-(1-\alpha) n F \eta / RT] \} \quad (2.1)$$

This equation expresses the mean current across an electrochemical interface in terms of the applied overpotential, η . The parameter i_0 is the exchange current at zero applied potential; α , the transfer coefficient, is a parameter related to the geometry of the activation energy barrier for dissolution; F is the Faraday constant, and n is the oxidation number of the dissolving species.

By applying a large enough anodic potential, we drive the system to the exponential region:

$$i \approx i_0 \exp[\alpha n F \eta / RT] \quad (2.2)$$

For a metal-ion electrode in this regime, the current is sustained by dissolution. To estimate the range of overpotentials at which expression (2.2) is valid, we need (for $\alpha = 1/2$ and $n = 1$)

$$\exp[F\eta/2RT] \gg \exp[-F\eta/2RT]$$

if we require

$$\frac{\exp[F\eta/2RT]}{\exp[-F\eta/2RT]} > .1$$

or, $\eta > 60 \text{ mV}$. This region of overpotentials is called the Tafel region.

In deriving the Butler-Volmer equation, an average activation energy for the elementary reduction-oxidation process is assumed. Although this proves to be a good approximation in the thermodynamic limit, since it allows the canonical treatment to provide us with the experimentally verifiable equation of dissolution (2.2), it is not unreasonable to question the possibility that the activation energy for dissolution be dependent on the local morphology where the anodic process is to take place.

Consider, for example, the one dimension surface model shown in figure 2.1. Each atom in the crystal lattice is represented by a square and the atoms at the surface exposed to an electrolyte are the uppermost square of each vertical column. We wish to compare the dissolution rate of the two atoms labeled A and B, by applying an overpotential η to the surface. To remove the atom B one must break one nearest neighbor bond and one next nearest neighbor bond. We then need to supply

$$\Delta E_B = nn_bond + nnn_bond$$

where nn_bond and nnn_bond are the energies of a nearest neighbor bond and a next nearest neighbor bond respectively.

Similarly, we can write for the A atom

$$\Delta E_A = 3nn_bond + 4nnn_bond$$

So even if $nn_bond \gg nnn_bond$, we would still have $\Delta E_A = 3\Delta E_B$. From classical rate theory, the rate V of the elementary dissolution process is such that

$$V \sim \exp(-\epsilon/k_bT)$$

where ϵ is the activation energy for the elementary process.

We conclude that surface sites of the type B can have a much higher dissolution rate than surface sites of type A, depending on the applied overpotential η .

Figure 2.1: One dimension model of a single crystal surface. Surface are represented by the shaded squares.

The influence of crystal structure on electrochemical parameters have been observed experimentally. Table 2.1, for instance, shows changes in the equilibrium electrode potential measured for various orientations of zinc surfaces.

Table 2.1: Equilibrium potential difference compared to polycrystalline for different Zn surface orientations.
Source [19].

	Potential difference compared to polycrystalline (mV)
Polycrystalline	0
(1211)	+4
(0001)	+1
(1010)	0
(1120)	-2
(1011)	+8

Although, in principal, this difference in potential could be due to a number of factors, different orientations expose different types of sites (in terms of their coordination

numbers). According to our one dimensional model of figure 2.4, we should expect different kinetics for different orientations.

Heusler et. al. [18,19] have performed experimental studies at iron surfaces and shown that mechanisms for dissolution can be dependent on surface structure. It is found, for instance, that the measured density of kinks on a monatomic step in the [211] direction increases with electrode potential. We will see that this result is also apparent on our simulations.

To include the influence of surface morphology in the Butler-Volmer equation, we propose, as a first approximation, the following equation of dissolution:

$$i_+ = A \sum_q n(q,t) \exp(-\Delta E(q)/k_b T) \quad (2.3)$$

where the “+” subscript indicates dissolution current. The sum index q scans all possible types of sites. For a model in which only nearest neighbors interactions are considered, q is the number of nearest neighbors of a particular surface atom. $\Delta E(q)$ is the activation energy which determines the kinetics of the dissolution of the site specified by q . The factors $n(q,t)$ are the instant density of q -type atoms and has units of number per unit area. Finally, the constant A preceding the equation has units of charge per unit time and, although it does not have any relation with the “decision” of whether a specific atom will dissolve, it plays a role in determining the time windows in which the event will happen.

An important feature of equation (2.3) is the time dependence of the population density $n(q,t)$. Consider again the one dimensional surface. Figure 2.2 shows two configurations representing the morphology of the surface before and after the dissolution of one atom. Below each surface, we show the statistics of the population before and after the dissolution process occurs in a time interval Δt .

We then notice that the dissolution of a site with $q = 1$ is accompanied by the increase in the population of sites with $q=2$. This way, the model can introduce fluctuations in the current due to fluctuations in the population density.

$$\frac{\partial i_+}{\partial t} = A \sum_q \frac{\partial n(q,t)}{\partial t} \exp(-\Delta E(q)/k_b T) \quad (2.4)$$

This source of noise has been simulated by Bellingham [22] by using stochastic simulations. The effects of a driving potential were not studied.

Figure 2.2: Surface morphology change due to dissolution of one atom.

Population of $q=2$ sites increases with decrease in population of $q=1$ site.

We expect that noise generated in this fashion, if detectable, will convey information on the surface morphology and, perhaps, its evolution. The important role of computer experiments is that one can monitor the surface structure evolution as the current is measured. Computer models of dissolution have also been studied by Sieradzki et. al. [23] for binary alloy surfaces; Kohli [24], Cheng and Coller[25], and Wehrli[4] for non driven (chemical) dissolution. In section 3 we describe in detail the aspects concerning the implementation of equations (2.3) and (2.4) for our simulations.

2.2 The Model

Structural stability of surfaces has been extensively investigated due to its importance in phenomena such as crystal growth. Models have been developed to explain

equilibrium and dynamic behavior of surface morphology and have provided an improved understanding of adsorption and desorption processes, surface diffusion and reaction mechanisms. Much of the work in this field involves computer simulations.

The simplest way to describe equilibrium configurations is to consider a (001) cubic surface in contact with its vapor. One can imagine a simple lattice gas situation with each site either being vacant or occupied by an atom whose interactions are limited to its nearest neighbors range. A further simplification consists of requiring that every occupied site be directly above another occupied site, a configuration sometimes referred to as solid-on-solid (SOS) [26,27]. A picture illustrating the model is shown in figure 2.3-a, where each atom is represented by a box. Surface atoms are topmost atoms of each column perpendicular to the (001) face.

Figure 2.3: a) The solid-on-solid model. Sites labeled with a k are kink sites, which have 3 nearest neighbors. Source [26]; b) Stepped surface generating a vicinal surface of the (001) orientation. Source [27].

At zero Kelvin, the surface is totally flat. For temperatures different from zero, corrugated structures are possible including steps and kinks. According to the number of nearest neighbors, the possible types of sites at an SOS surface are listed on table 2.2.

Vicinal surfaces can be generated in the SOS model by conveniently placing monoatomic steps (figure 2.3-b).

Table 2.2: Types of sites on an SOS surface.

nearest neighbors	site
5	terrace
4	ledge
3	kink
2	at-ledge
1	adatom

Equilibrium statistical mechanics is studied on the SOS by writing the Hamiltonian for the system:

$$E = E_0 - \frac{\phi}{2} \sum_{i,\delta} \min(h_i, h_{i+\delta}) - \phi \sum_i h_i \quad (2.5)$$

where the indices i run over all possible vertical columns and $i + \delta$ label the neighboring columns of i . The coefficient ϕ is the energy of the nearest neighbor interaction between atoms which is considered to be equal for the vertical and lateral bonds. The heights, h_i 's, are measured with respect to the zero temperature flat level where all h_i 's are zero for all i 's, when the energy of the crystal is E_0 . The second term on the left hand side represents all lateral bonds that have been broken, and the factor $1/2$ allows for overcounting in the sum. The last term represents broken or constructed vertical bonds.

Although the SOS model is simple and has a well defined Hamiltonian (2.5), its partition function cannot be calculated analytically. Like the three-dimensional Ising model for spin systems, thermodynamic quantities are estimated via Monte Carlo calculations. Much progress in understanding this model has been made using this method[26,27].

Our surface for simulation of electrochemical dissolution is a (001) SOS crystal of dimensions $L \times L \times \infty$. For most of our experiments, L is taken to be equal to 32 or 64, and with an infinite third dimension allows continuous dissolution. The surface is simulated by a 2×2 matrix which is mapped into a linear array of size L^2 as shown in Figure 2.4. Dissolution of one surface atom is accomplished by adding 1 to the respective site position in the array. Periodic boundary conditions are added to the system, so that an

atom in the right-most column interacts with the atom which is in the left-most column and on the same row (Figure 2.4). Similarly, atoms on the top row interact with atoms on the bottom row. This a standard procedure used for finite systems to simulate infinite structures - any atom can be taken to be the center . In this way, the number of nearest neighbors of a specific site can be calculated by comparing the integer saved in the site's array position with the integers in the nearest neighbors positions.

Figure 2.4: Linear array used to map the SOS model ($L = 4$).
Boundary conditions are added to the system as indicated

We then consider the situation in which energy is constantly given to the atoms at the SOS surface by electrochemically applying an anodic overpotential to the electrode. If the polarization is large enough, we saw in equation (2.1) that it is reasonable to consider that the only process occurring at the interface is the dissolution of atoms from the surface. We chose to work on the region of potentials such that:

$$1 < \frac{eV}{k_b T} < 5$$

where $T = 25^\circ\text{C}$ and is kept constant for all experiments, and k_b is the Boltzmann constant. In terms of volts we then have:

$$25.7 \text{ mV} < V < 125.5 \text{ mV}$$

By using values for the potential in this range, we expect to drive the system to the exponential regime of the Butler-Volmer equation as calculated in equation (2.1) for

$\alpha = 1/2$. We also assume that atoms dissolve with charge +1. The interaction energy between nearest neighbors is kept constant for all experiments and was set equal to

$$\frac{\phi}{k_b T} = 1.95 \quad \text{or} \quad \phi = .05 \text{ eV}$$

From here on, the word *potential* will refer to the quantity $\frac{eV}{k_b T}$.

The basic assumption of our model is that all atoms at the surface experience the same electric field, which can be applied due to the nature of the interface. This way, we alter the Hamiltonian (2.5), biasing the probabilities of dissolution. The Monte Carlo method was then implemented in the following way: an atom was chosen at random and the number of nearest neighbors nn was calculated. The probability of dissolution was then assigned according to

$$\Delta E = nn \frac{\phi}{k_b T} - \frac{eV}{k_b T} \quad (2.6)$$

For the case of $\Delta E < 0$, the atom was dissolved. For $\Delta E > 0$, a random number was generated and compared to $\exp[-\Delta E/k_b T]$.

Note that, in this model, the activation energy is assumed to be related to the number of nearest neighbors. We do not imply that it is determined by the total bond energy, only that there is a relationship between activation energy as a function of nearest neighbors.

2.3 Width Measurements

The first parameter studied in our simulations is the width of the surface. This parameter is similar to the surface roughness and for one specific surface configuration, the average height is defined as:

$$\bar{h} = \frac{1}{L^2} \sum_i h_i \quad (2.7)$$

where i labels all vertical columns in the SOS model. The width of the surface is defined as

$$w = \sqrt{\frac{1}{L^2} \sum_i (h_i - \bar{h})^2} \quad (2.8)$$

and provides a measurement of the surface thickness.

Figure 2.5 shows a typical time evolution of the surface width for $L=32$ and $\frac{eV}{k_bT} = 2$. The surface is originally flat and the width is calculated every 2000 dissolution attempts. Notice that the width approaches a steady state mean value around which fluctuations occur. Figure 2.6 shows plots for a $L=64$ lattice as a function of applied potential, $\frac{eV}{k_bT}$. The values are plotted as a function of time in units of Monte Carlo steps (mcs) - one mcs corresponds, on average, to a complete visit to all surface lattice sites. All plots are average of 500 independent runs. The system reaches steady state after approximately 500 mcs for high values of potential; for low potential steady state does not seem to occur before 1000 mcs.

Figure 2.7 is the time evolution of the width for $L=32$ for two potentials. The average value of the width for the higher potential ($\frac{eV}{k_bT} = 6$) is greater than that of the lower potential ($\frac{eV}{k_bT} = 2$). A less straightforward feature of this plot is the fluctuations around the mean value: notice that for potential equal to 6, the surface undergoes larger fluctuations on the width. Figure 2.8 shows the transition of steady-states from $\frac{eV}{k_bT} = 3$ to $\frac{eV}{k_bT} = 5$ during one run. The increase on the size of width fluctuations are easily noticed.

In Figure 2.9 we plot average values of the width for potentials varying from 2 to 5. The reported error bars are statistical errors from averaging 10 potential scans. In each run, we start with a flat surface at potential equal to 1. To start the calculation of the next value of potential, we use as initial condition the resulting surface morphology of the previous value of potential. After steady-state is reached, average values are calculated for 15000 mcs. The curves show increasing values of width with increasing values of potential. Figure 2.10 plots results for potentials between 5 and 7 and confirms the trend. We observe that the value for the width at steady-state is a function of the size of the lattice. For larger lattices, larger values of width are measured for the same applied interface potential.

Finite size effects are widely observed in physical models that study interacting systems using finite lattices. An important application of renormalization group theories has been in determining functional laws that govern the way in which thermodynamic quantities

Figure 2.5: Width of surface as a function of time (in units of dissolution steps). $L=32$ and potential equals 2.

Figure 2.6: Width transients for various potential values; $L=64$.

Figure 2.7: Width of surface as a function of time (in units of of dissolution steps). $L=32$ and potential equals 2 ("o") and 6("*").

Figure 2.8: Width of surface as a function of time (in units of of dissolution steps). $L=32$ and potential changes from 3 to 5 at 4×10^6 .

Figure 2.9: Width measurements for potentials between 2 and 5.

Figure 2.10: Width measurements for potentials between 5 and 7. $L=32$.

scale with the size of the system. These theoretical methods have been applied to the study of non-equilibrium growth models, such as ballistic growth [28,29], and it has been determined that at steady state the width of the growing interface scales as a power law

$$w \sim L^\alpha$$

where α is to be calculated. Verification of this law for our system remains to be performed. Figure 2.11 shows plots of width transients for different lattice sizes at a potential of 4.5. Notice that for $L=256$ and $L=128$ the system does not reach steady state before 1000 mcs. This is also observed in crystal growth models [29], but remains to be understood in the context of our dissolution model.

2.4 Site Statistics

The idea on performing the measurements reported in this section is to monitor the contribution of each type of site to the current as defined in equation (2.3). We define the population density of a specific type of site to be the fraction of the surface occupied by it. So, for example, the density of kinks is

$$\text{density of kinks} = \frac{\text{number of kinks}}{L^2}$$

Figure 2.12 shows population densities for all sites. For a fixed value of potential, the population increases with the coordination number nn . No considerable change is observed in the population of ledges ($nn = 4$). The population of all other types of sites, however, show either an increasing ($nn = 1, 2, 3$) or decreasing ($nn = 5$) trend for increasing potentials.

Over the range of potentials from 1 to 4, low coordination sites $nn = 1$ and $nn = 2$, increase in population by more than 4 times (Figures 2.13-a and 2.13-b), which is reflected in a small decrease on the population density of terraces (Figure 2.13-d). For this range of potentials, the population of kinks is not affected very much. However, at $\frac{eV}{k_b T} = 4$ an abrupt change in the slope of terrace density accompanies an abrupt change in the slope of kink population (Figure 2.13-c). From Figure 2.12 we see no special change in behavior for the $nn = 1$ and $nn = 2$ curves at this potential.

Figure 2.11: Width transients for various lattice sites. Potential equals 4.5.

Figure 2.12: Population density for all type of sites on the SOS surface.

Figure 2.13: Population density for adatoms ($nn = 1$, (a)) and for at-ledges ($nn = 2$, (b)).

Figure 2.13: Population density for kinks ($nn = 3$, (c)) and for terraces ($nn = 5$, (d)).

It is important to note the change in behavior of the width curve observed in Figure 2.9 for some value of potential around $\frac{eV}{k_bT} = 4$. For potentials less than 4, the sum of populations of kinks, at-ledges, and adatoms is approximately 10%. It then increases considerably and reaches a value of approximately 25% when the potential equals 5. Therefore, it seems that the surface becomes much rougher at $\frac{eV}{k_bT} = 4$. Further data (section 2.4) will support this conclusion.

To analyze the contribution of the different type of sites to the dissolution current, it is of major importance to note that the population density is not the only relevant factor. Recalling equation (2.3):

$$i_+ = A \sum_q n(q,t) \exp(-\Delta E(q)/k_bT) \quad (2.3)$$

we notice that the exponential factors also play an important role. We define the dissolution rate of a site with nn nearest neighbors to be

$$v(nn) = n(q,t) \exp(-\Delta E(q)/k_bT) \quad (2.9)$$

which, although not having units of rate, measures the relative contribution of the nn-type site to the total anodic current.

Figure 2.14 plots dissolution rates for the 5 types of lattice sites as a function of potential. We notice first that, although always having a large population, terraces (nn = 5) contribute the least to the current over this range of potentials. This is solely due to their small dissolution probability.

The most important feature of this plot is that it shows a change in behavior in the dissolution process at a potential value of about 2.5, where the nn = 1 and nn = 2 curves intersect that of the kinks, nn = 3 (not necessarily at the same point). From this fact, we conclude that at low potentials, kinks contribute most to the electrical current. This regime is of low current density, and one can infer propagation of kink sites along steps generating dissolution. For large enough potentials, the large rate of dissolution of adatoms and at-ledges, together with their increasing population density, make these sites the dominant

Figure 2.14: Dissolution rate (as defined in equation (2.9)) for all type of sites.

dissolution sites. These results illustrate important changes in the steady state surface morphology as a function of applied potential.

2.5 Surface Morphology

In section 2.3 showed that the surface model undergoes a change in the population density trend at a value of the applied potential close to 4, and that at this potential, the curve of width as a function of potential also show a change in behavior. To better see the effect of these changes on the morphology of the surface, we show here results of two-dimension fourier transforms as well as "photographs" of representative surfaces for several values of potential. All results here are for $L=128$ lattices.

In general, for a two-dimension lattice of size L defined by x and y coordinates and assuming values

$$-\frac{L}{2} < x \leq \frac{L}{2} \quad -\frac{L}{2} < y \leq \frac{L}{2}$$

the discrete fourier transform assume values of frequencies

$$f_x = \frac{1}{L}k_x \quad f_y = \frac{1}{L}k_y$$

with

$$-\frac{L}{2} < k_x \leq \frac{L}{2} \quad -\frac{L}{2} < k_y \leq \frac{L}{2}$$

Since we do not expect the spectrum to depend on the direction of k , we report power as a function of

$$k = \sqrt{k_x^2 + k_y^2} \quad (2.10)$$

Figure 2.15 shows the low frequency spectra for different values of potential. The symbol v denotes the potential $\frac{eV}{k_b T}$. The important feature is the fact that the surface morphology has high power contributions at low frequency for potentials from 2 to 6.

The high frequency spectra are shown in Figure 2.16. For potentials from 1 to 3 (Figure 2.16-a) we see no major differences. In fact, we believe that the apparent trend of decreasing high frequency power for increasing potentials can be eliminated by calculating and averaging more spectra. This conclusion is supported by observation of Figure 2.16-b,

Figure 2.15: Low frequency spectrum of surface for potentials from 1 to 3 (a) and from 3 to 5 (b).

Figure 2.16: High frequency spectrum of surface for potentials from 1 to 3 (a) and from 3 to 5 (b).

where, for potentials greater than 4, the high frequency spectrum increases abruptly. This should be related to the increasing number of kink sites and the change in behavior of width vs potential curves at $\frac{eV}{k_b T} = 4$. Notice also the tail of the spectrum for $k > 64$ due to the square geometry of the lattice.

Results of the power spectra are better appreciated by observing the series of Figures 2.17-a to 2.17-d, which are “photographs” of the surfaces taken during steady-state. The lattice size, L , is 128 and darker gray tones qualitatively represent deeper levels at the surface. Note that no information of width can be extracted from these pictures.

Qualitative analysis of the high frequency spectrum can be carried out if we go from one end of the surface to the other and “count” the number of times the gray level changes. We then notice that this number increases for potential values from 2 to 4, but increases abruptly from 4 to 5. This is reflected in the spectrum of Figure 2.16-b. Note that for potential equal to 4 we can still identify large flat regions which are not present when the potential equals 5.

With careful observation of Figure 2.16-d, we can see that, although very rough, the surface has regions of light gray tones which are reasonably large (“hills”) with neighbor regions of dark gray tones which are also reasonably large (“valleys”). This corresponds to long wavelengths variations of the surface height, which explains the power at low k values (Figure 2.15b).

2.6 Summary

In summary, we have implemented simulations of metal dissolution using Monte Carlo technique. In preliminary results, we have demonstrated the validity of this approach and shown that new insights can be gained from theoretical modelling of dissolution processes. In particular, we have shown that:

- i) the steady state width of the surface increases with increasing applied potential;
- ii) the steady state width contains fluctuations related to the dynamic nature of the dissolution process;

iii) for the conditions used in the model, a sharp increase in the steady state width is observed at a potential of 4 (eV/kT). Similar transitions are observed during deposition processes and we will explore this aspect in future work (section 3);

iv) the steady-state width is a function of lattice size, L . This is consistent with other simulation work, and we are currently examining the form of this dependence in comparison to existing theories; and

v) The concentration of surface lattice sites are dependent on potential. This observation is important in determining the contribution of surface sites to the dissolution current. We find that at low potentials, we observe kinks are the most active sites for dissolution, while at high potentials other low coordination sites also become important due to the continuous roughening of the surface.

Figure 2.17-a: Surface “photograph” for potential equal to 2.
Darker tones denote deeper regions.

Figure 2.17-b: Surface “photograph” for potential equal to 3.
Darker tones denote deeper regions.

Figure 2.17-c: Surface “photograph” for potential equal to 4.
Darker tones denote deeper regions.

Figure 2.17.d: Surface "photograph" for potential equal to 5.
Darker tones denote deeper regions.

3 - Future Research

3.1 Approach

The evolution of rough structures on surfaces is observed in a number of important physical and chemical processes in which material is removed from a surface. Examples of such processes are erosion, electropolishing, and corrosion [29,30]. Increased understanding of crystal growth has revealed that rough surfaces are also formed during processes in which material is added to the system. The evolution of interface morphologies has therefore been the subject of intensive fundamental research, of which the driving force is to understand and predict the dynamic and static aspects of roughening, as well as possible universal characteristics independent of the particular model used.

An important feature learned from the results of crystal growth simulations is the distinction between two different mechanisms of growth [26]: at low temperatures, nucleation controlled growth is observed, in which stable islands of deposited atoms must be formed - the nucleation process is the rate determining step. Above a certain temperature, T_R , the system enters a continuous growth regime when the nucleation barrier disappears. The change in the growth mechanism is due to a fundamental process which is called the roughening transition. At T_R the system undergoes this characteristic phase transition, which is of higher order (no latent heat), and can be characterized by the vanishing of the step free energy F_s . When $F_s = 0$, the surface sees no energy barrier for the creation of steps. It then becomes rough and atomic clusters of all sizes can be found on the surface of an infinite system. For finite models, the sizes of these clusters, as well as the sizes of the steps, will be limited.

The roughening temperature is actually believed to be a function of the external driving force which controls the growth [31,32]. For large values of the driving force, the transition occurs at temperatures which are lower than the roughening temperature of the system in equilibrium with its vapor. This kinetic roughening has been investigated by several authors [32-35] and it may have important consequences in determining optimal growth conditions to attain a specific surface morphology. Phillips and Chrzan [35] recently proposed the construction of a kinetic phase diagram on which different growth behaviors, characterized by scaling exponents, can be shown as a function of kinetic parameters. The scaling exponents, will be discussed later in section 3.3, determine universal characteristics of growth processes, regardless of the particular features of the model under investigation. Calculation of these exponents via computer simulation has

been carried out for several models such as the Random Deposition Model, Ballistic Deposition Model, and the Eden Model [29]. Analytical treatments available in the literature are generally based on the modified versions of the Langevin equation [29,34].

We envision the problem addressed by this proposal as a modified version, perhaps a more complex one, of the problems investigated by crystal growth scientists. Our fundamental point is that much of the kinetics of electrochemical processes occurring at a metal-electrolyte interface is dependent on the morphology of the metal surfaces. If this is the case, then one might expect that information on the kinetics of these processes is left as characteristic structure on the surfaces.

All present kinetic theories of electrochemical processes neglect the influence of surface morphology and its fluctuations. In fact, for the case of corrosion, we are left with the approach proposed by Wagner and Traud [6] in which the Butler-Volmer equation is applied to a heterogeneous process where the oxidation and reduction reactions originate from different processes. In this approach, the single electrode equilibrium potential is transposed to an open-circuit corrosion potential (E_{corr}) and the exchange current density to the corrosion current (i_{corr}). Under open-circuit conditions, both anodic dissolution and cathodic reduction must occur simultaneously on the metal surface. Therefore, it has been inferred that anode and cathode areas are randomly distributed over an electrode surface. In order to attain a uniform thinning (uniform corrosion), the anode and cathode areas must be dynamic and the accepted concept of uniform corrosion is one of 'shifting' anodes and cathodes. However, the concept of fluctuating anodes and cathodes cannot be built in a phenomenological theory based on the Butler-Volmer equation, which contains no information on local surface properties. As we have shown in the previous section, for the specific case of driven dissolution, as we have modeled it, sites with low coordination number are 'more anodic' than sites with high coordination number, in the sense that the former contributes more to the anodic current than the latter. If local properties control the anodic process, we may expect that fluctuations of the surface morphology are coupled with fluctuations on reaction site specificity, and consequently with the shifting of anodes and cathodes.

Several other results from our previous simulations illustrate the fact that morphological aspects are of importance on electrode kinetics. The width of the interface, for instance, is a measure of the correlation between the atoms along the z-direction. We show that this correlation is dependent on the application of an external field. As a

consequence of this mechanism, the surface becomes rougher with more low coordination sites. Heusler et. al. [20,21] have experimentally verified that the density of kinks increases with increasing anodic potentials during dissolution of iron. Another interesting aspect is the change on the behavior of the width versus anodic potential curve at some value of potential, which might be evidence for the existence of a kinetic roughening transition in these systems. We also have shown that the classical picture of dissolution with propagating kink sites along a step is only valid in our model for low values of potential, and might deserve some further discussion.

We therefore propose to continue our investigation of how surface morphologies influence electrode kinetics, by addressing the questions posed by our previous results. We believe that we now understand more basic mechanisms important for driven dissolution, even though we have used simplistic models for interactions at the electrochemical interface. A more fundamental justification of these interactions remains to be performed, perhaps by comparing experimental data from the literature to accessible quantities of the model, such as activation energy for dissolution. We are also fortunate that atomic resolution microscopy (e.g. Scanning Tunneling Microscopy and Atomic Force Microscopy) is becoming more advanced as an experimental tool for verification of possible theories that address surface morphology aspects of this problem.

3.2 Morphological Aspects of Surface Kinetics

Much progress in understanding dissolution kinetics is presently being achieved with studies of weathering and related processes [2-5]. Chemical weathering is the natural dissolution of minerals in contact with aqueous solutions, and it occurs where the chemical composition of the solid is not in equilibrium with the aqueous phase. Due to the importance of weathering in the global cycle of elements, the kinetics of processes at the mineral-water interface is of considerable importance. Although some issues in this field are still under debate [3], these studies have shown that surface processes control the kinetics of dissolution of oxides and silicates, and that their rates are extremely dependent on the local coordination chemistry within the surface.

Experimental data have verified that dissolution of some oxides in acidic solutions follows proton-assisted mechanism [5]: protons bind to oxide ions at the surface and

weaken the necessary bonds to promote dissolution. Figure 3.1 is a schematic representation of a such possible mechanism.

Figure 3.1 - Representation of a hypothetical proto-assisted dissolution mechanism. From [36].

The adsorption of protons to the surface is believed to be fast and it is assumed that the concentration x_H of surface protons is in equilibrium with solution. The rate determining step is thought to be the detachment of the metal ion. Wieland et. al [2] have proposed a statistical model with which it is possible to calculate the rate of the dissolution reaction. They assume a random distribution of excess protons among surface oxide ions. The probability x_{nj} of finding a metal site of coordination n surrounded by j excess protons is given by the binomial distribution:

$$x_{nj} = \binom{n}{j} (x_H)^j (1 - x_H)^{n-j} \quad (3.1)$$

The total rate of dissolution will then be given by

$$R_H = \sum_n \sum_j k_{nj} x_n x_{nj} S \quad (3.2)$$

where S is the surface density of sites and x_n is the fraction of n -type site. The k_{nj} 's are rate constants for dissolution promoted by j protons of sites with n ligands. The sum label n scans all possible types of sites; j scans the number of precursor protons dependent on

the reaction mechanism, which also depends on n . Different mechanisms for different surface sites characterized by n imply different activation energies which express their tendency to dissolve - the most active sites are those with lowest activation energies. The dissolution reactions [2]:

are, evidently, parallel reactions. Therefore, we rewrite equation (2.2) as

$$R_H = \sum_{\substack{a \in \\ \text{(active sites)}}} k_{ja} x_a x_{ja} S \quad (3.3)$$

where {active sites} is the set of type of sites with comparatively fast kinetics. The index j is assumed to be unique for each different active site. Experimental evidence supports [2,3] the hypothesis that dissolution kinetics is controlled by only one of the parallel reactions.

Morphological aspects of the surface will control the type and the concentration of active sites. Wehrli et. al [2] have recently reported anisotropic dissolution kinetics of kaolinite. It is found that the strong anisotropy is due to different mechanisms of protonation of the three distinct crystal surfaces studied, because different geometries expose different active sites. In the same paper, these authors studied the influence of adsorbed cationic species, VO^{2+} , on a dissolving surface of $\delta\text{-Al}_2\text{O}_3$. Even at low surface concentrations, VO^{2+} inhibits proton-promoted dissolution (to about 60%), which is not significantly altered by increasing concentration of adsorbed VO^{2+} . Therefore, it is proposed that two different types of sites are active in the dissolution process, and one type is preferentially blocked by VO^{2+} . Equation (3.3) can then be modified to include the effect of adsorbed species

$$R_H = k_{ja} x_a (1 - x_M) x_{ja} S \quad (3.4)$$

where x_M is the mol fraction of blocked active sites. Equation (3.4) fits very well the available their experimental data [3].

Unlike mineral dissolution, processes on metal surfaces present much faster kinetics, and they proceed in the presence of strong electric fields. Mechanisms of surface reactions are, therefore, likely to be different, introducing other complexities to our treatment. Nevertheless, general aspects of the mineral dissolution process should be readily transposed. The concept of active dissolution sites, for instance, is not new in electrochemistry. Frankenthal [37] carried studies on the passivation of iron-chromium alloys and observed that a very small coverage of the surface affords a high degree of protection: for a surface coverage of 1.1%, the anodic current is reduced to 1% of its value when no passivation occurs. Passivation is then simply the deactivation of active sites due to adsorption or chemical reactions. Indeed, it is well known that the passivation processes for metals such as Cr, Ni, Pt, and Pd are initiated by electrochemisorption of oxygen or hydroxide ions [62].

We can also conclude from equation (3.4), that a constant dissolution rate may imply that the number of active sites does not change and the surface then must feature some kind of steady-state morphology. Wehrli [4] carried out computer experiments of oxide dissolution with kinetics based on simulated coordination chemistry of the solid-on-solid model (see section 2.2), and it was verified that a constant roughness is generated. Our simulation results strongly support these conclusions. Furthermore, we show how morphologies, and therefore the population of active sites, are strongly dependent on the thermodynamic variables of the system, such as the external applied electrical potential.

3.3 Simulation of Metal Dissolution

The proposed research project will focus in further development of the computational model already implemented. We will continue to address problems concerning metal dissolution mechanisms, particularly the influence of an externally applied potential. Computer simulations are justified not only when used to elucidate subtle mechanisms, but mostly when the mathematics is very complex, if not intractable. The solid-on-solid model has an Ising-like Hamiltonian, whose partition function has not yet been solved analytically. Therefore, all equilibrium and non-equilibrium results obtained to date with this model are numerical.

3.3.1 Surface Scaling and Phase Transitions

In general, when estimating thermodynamic quantities from numerical simulations of equilibrium Statistical Mechanics on small systems, one needs to perform a finite size scaling analysis [38]. This analysis is used to search for the dependence of the calculated quantities on the linear dimension L of the system under investigation. The quantities can then be extrapolated to values representative of a thermodynamic system.

With motivation on the fact that non-equilibrium interface growth processes generally reach steady state conditions with structures that resemble much those of fractals, a general scaling approach [29] has been developed for describing growing interfaces. The importance of this approach is that it determines quantities, i.e. exponents, which are not unique to the process under investigation, but has a universal character, independent on the particular features of individual growth models. Due to the similarities of our dissolution model to the recently published growth studies, we wish to investigate the extent to which scaling theories apply to our system.

The dynamic scaling approach [29] considers a flat surface at $t=0$ which is allowed to grow by some pre-defined stochastic growth laws. Information of the surface morphology is controlled by the function $h(x,t)$ which gives the height at the surface position x at time t . The surface width (see section 2.3) is measured by:

$$w = \sqrt{\frac{1}{L^d} \sum_i (h_i - \bar{h})^2} \quad (2.8)$$

where d is the dimension of the surface and $\bar{h}$ is the average height which is given by:

$$\bar{h} = \frac{1}{L^d} \sum_i h_i \quad (2.7)$$

Initially, the surface roughens as a consequence of the build-up of random fluctuations on $h(x,t)$. The width of the interface therefore grows as a function of time, and it measures the correlation among these fluctuations along the growth direction. When the size of the fluctuations become comparable to L , the width reaches a steady-state value. The dependence of $w(L, t)$ on t and L is thought of to be of the form [29]

$$w(L, t) \approx L^\alpha f(t/L^{\alpha/\beta}) \quad (3.5)$$

where f is a function such that

$$f(x) \approx x^\beta \quad \text{for } x \ll 1 \quad (3.6)$$

$$f(x) = \text{constant} \quad \text{for } x \gg 1 \quad (3.7)$$

Then, for small times in the simulation, one expects $w \approx t^\beta$, and after reaching steady-state, $w \approx L^\alpha$. Several estimates for these exponents exist from numerical simulations [32,33,39] and analytical studies [34]. Although results for one dimensional surfaces seem to agree well, some questions on universalities for two dimensional surfaces are still unanswered [29,39].

Our results in Figures 2.6 and 2.11 show that surfaces undergoing driven dissolution might show scaling behavior similar of that proposed by equation 3.5. The identification of universality classes of rough surfaces given by the exponents may be of practical importance [29,35] in which they characterize possible interfaces. Surface roughness is an important experimental parameter in electrochemistry, principally in studies of impedance measurements. Theoretical and experimental investigations[40-42] have tried to relate the response of fractal-like electrodes to fractal dimensions. During our research, we intend to study the scaling features of a dissolving metal surfaces in detail to include the influence of the applied potential.

Along with the study of the scaling behavior of growing rough surfaces, the possibility of existence of a kinetic roughening transition (KRT) has been investigated by several authors [32-35]. The KRT is the non-equilibrium analog [34] of the *equilibrium* roughening transition (ERT) which is known to occur in interfacial systems in equilibrium, e.g. solid and vapor equilibrium: smooth facets dominate the morphology at low temperatures, and the surface becomes rough at high temperatures. Perhaps the most convincing evidence for the existence of these transitions during interfacial growth has been published by Amar and Family [33]. They find two growth regimes for low and high temperatures, characterized by distinct exponents. These regimes were found to be

separated by a region of temperatures in which logarithmic growth is observed ($w^2 \approx \log t$ at transient, $w^2 \approx \log L$ at saturation) which is characteristic of the ERT.

Figure 2.9 shows the abrupt change in behavior of the width parameter as a function of the applied potential, which might be an indication of such a phase transition in our dissolution system. Guo, Grossman, and Grant [32], have studied a growth model in which probabilities are biased by a parameter λ_a ($\text{prob} \sim \exp(-\Delta E/kT + \lambda_a)$) corresponding to an external field. When $\lambda_a = 0$, ERT is recovered. Simulations at a constant temperature show a phase transition for a fixed value of λ_a . Our model is similar to this, in which the probabilities are biased in the same way. A possible kinetic roughening phase transition in electrochemically dissolving systems can be of much interest, since only very few roughening phenomena have been observed experimentally. Most of the experiments have been carried out on ^4He [43].

The wide spectrum of interesting and technologically important electrochemical phenomena which are related to interface structure are only now being subject of intensive research. Recently published Atomic Force Microscopy images of Cu monolayer electrodeposited Ag(111) [44], for instance, give evidence for an electrochemical induced surface reconstruction, which is dependent on the electrolyte used: depositions under 0.1 M perchlorate acid result in (111)Cu monolayer, but rotated ($\sim 30^\circ$) with respect with the Ag surface; depositions under 0.1 M sulfate (same potential as with perchlorate solution) feature a $(\sqrt{3} \times \sqrt{3})R30^\circ$ reconstructed structure of Cu on Ag. Theoretical understanding of these results are in progress.

3.3.2 Site Dependent Activation Energies

Apart from the physical aspects of driven dissolution discussed in section 3.3.1, our studies will modify the present model to simulate more realistic systems. From a practical point of view, we are interested in generating kinetic data to be compared to experimental results. Quantities like reaction rates, as well as their mechanisms, free energies and transfer coefficients are, therefore, important parameters to serve as input to our simulations. The dissolution chemistry of many metals have been extensively studied. Zinc is likely to be selected as a metal for our simulations since it corrodes almost exclusively with hydrogen evolution in acid solutions, thereby avoiding consideration of oxygen reduction as a cathodic process. Other metals of interest are: the group IB elements

(Cu, Ag, Au), Cd, Ga and Cr. The group IB elements are noble metals and can be studied close to the equilibrium potential in absence of other electrode reactions. The kinetics of silver dissolution are also well established, especially with regard to amalgams. Cadmium is of interest because it is another metal with well defined and relatively simple dissolution kinetics. Gallium is an element of recent technological interest, principally with respect to etching. It also has the advantage of having a melting point near room temperature and can, therefore, be easily studied in the liquid state. Chromium is another metal of technological importance, primarily due to its passivation characteristics, and is included in order to study the passivation mechanism close to the Flade potential.

Zinc dissolution in acidic solutions is generally accepted to proceed by two consecutive one-electron reactions:

The reaction rate is determined by solvation of the zinc ion:

At the equilibrium potential, the exchange current density, i_0 , is given by:

$$i_0 = nFk_+(c_M)^\alpha (c_M^{n+})^{1-\alpha} \quad (3.10)$$

For solid polycrystalline zinc in ClO_4^- solution, the exchange current density has been reported to be in the range $3.2 - 3.7 \times 10^{-4} \text{ A/cm}^2$ depending upon the concentration of Zn^{2+} [45]. The results from impedance measurements [45] indicated that the concentration of surface active sites, c_M , was 1×10^{-5} of the total surface. Assuming a surface concentration of $10^{15} \text{ atoms/cm}^2$, c_M can be estimated to be on the order of $10^{10} / \text{cm}^2$. If $\alpha = 1$, then an apparent rate constant of $1.55 \times 10^{-3} \text{ cm/s}$ is calculated [45]. This value is in good agreement with rate constants calculated for zinc dissolution from amalgam electrodes [45-48]. As we have shown (see section 2.3), the density of active dissolution sites is readily accessible from our models, and can be incorporated into some of the phenomenological equations as 3.10.

The anodic rate constant, k_+ , is given by:

$$k_+ = B \exp(-\Delta H^*/RT) \quad (3.11)$$

where the pre-exponential constant, B , is a factor representing the number of attempts at overcoming the activation dissolution barrier. B includes entropic changes, and can be calculated from the rate constant k_+ and the heat of activation ΔH^* . For the case of zinc dissolution from amalgam, B has been found to be in the range $1-100 \times 10^4$ cm/s [47,48] depending upon anion and ionic strength. The heat of activation can be measured from the temperature dependence of the exchange current density:

$$\Delta H^* = 2.303R \frac{\partial \log i_0}{\partial (1/T)} \quad (3.12)$$

For zinc dissolution from a solid electrode in ClO_4^- solution, Clark and Hampson [45] reported $\Delta H^* = 21$ kJ/mol. In comparison, ΔH^* for dissolution from an amalgam was found to be 42 kJ/mol in ClO_4^- solution. In other halide solutions, ΔH^* was reported to be in the range 30 - 46 kJ/mol [46,48]. These values were found to be relatively independent of ionic strength. Clark and Hampson [45] estimated the activation energy for zinc dissolution from a solid electrode by calculating the entropy of the transition state [49]:

$$i_0 = 9.6 \times 10^8 \exp(\Delta S^*/R) \exp(-\Delta H^*/RT) \quad (3.13)$$

Assuming that only a fraction of the surface was active (1×10^{-5}), ΔS^* was estimated to be -55 J/Kmol. From this value, the activation energy for zinc dissolution was calculated to be 37 kJ/mol.

The kinetic Monte Carlo method models rate equations as stochastic processes in which probabilities for possible events are assigned according to the energetics of the elementary processes [38,50]. In general, these probabilities are related to principle of microscopic reversibility, which require that the rates of forward and reverse elementary processes be the same at equilibrium:

$$P_i W_{ij} = P_j W_{ji} \quad (3.14)$$

where P_i is the probability of finding the system at a configuration labeled by i , $P_i \sim \exp(-E_i/kT)$; W_{ij} is the rate at which the transition from configurations i to j occur. The rates W_{ij} 's are related to the activation energy of the transition, and their ratios determine the probabilities necessary for the Monte Carlo simulation:

$$\frac{W_{ij}}{W_{ji}} = \frac{P_j}{P_i} = \exp(-(E_j - E_i)/kT) \quad (3.15)$$

which is only a function of the difference of internal energies of configuration i and j .

Experimental data can be brought into the simulation by relating the difference $E_j - E_i$ to the activation enthalpy change in the process, ΔH_{ij} . In our specific case of dissolution of one atom, we have interpreted the change in enthalpy to be the energy necessary to break number of nearest neighbor bonds of the surface atom:

$$\Delta H = n\Phi_{ss} \quad (3.16)$$

where Φ_{ss} is the solid-solid bonding energy of two neighbors. To account for the effect of electrolyte in the complex dissolution processes of oxides, Blum and Lasaga [50] write the expression above as

$$\Delta H = n\Phi \quad (3.17)$$

with

$$\Phi = 2\Phi_{sf} - \Phi_{ss} - \Phi_{ff} \quad (3.18)$$

to represent a mechanism in which the dissolution of an adatom ($n = 1$) would involve breaking one solid-solid bond, one fluid-fluid bond, and forming two solid-fluid bonds. As shown above for the case of Zn, the heat of dissolution (activation enthalpy), ΔH_{diss} , is a measurable parameter. It can be used to estimate the parameter Φ , regardless of the mechanism of dissolution

$$\Phi = 2 \frac{\Delta H_{diss}}{q} \quad (3.19)$$

where q is taken [50] as the coordination of the crystal, i.e. for a simple cubic, $\Phi = \Delta H_{\text{diss}}/3$. Due to the fact that only surface atoms participate in the dissolution process, q is more likely to be less than the bulk value. Incorporating this type of experimental data together with real lattices, such as BCC and FCC, is our first approach towards simulating real systems.

The experimental values obtained for ΔH_{diss} are phenomenological measures of the change in the interaction energies when the atom goes from the surface to the solution, and include all steps of the dissolution mechanism. In a first attempt to study the problem with a simple microscopic treatment, we have approximated the heat of dissolution to be solely the bonding energy of the surface atom, and we have neglected interactions other than first nearest neighbors. It was also assumed that all atoms at the surface, independent of the local morphology, feel the same electric field applied via anodic polarization. All electrochemistry is then simulated by the potential energy due to the applied field, which competes with the bonding energy in trying to remove the atom from the surface. Considerations of morphology in this model are, therefore, taken only with respect to the first nearest neighbors in the attractive part of the atom energy. We envision a deeper understanding of the morphological aspects of surface kinetics by considering the following aspects:

- 1) the role of the second nearest neighbors in the surface atom bonding energy; and
- 2) the extent to which surface morphology affects the applied electric field, and possible consequences in the dissolution kinetics.

Finnis [51] suggested a way in which the bonding energy of an atomic site can be calculated by considering the local number of neighbors. The total energy of the atom is

$$u_{\text{tot}} = u_N + u_p \quad (3.20)$$

The potential energy u_N is attractive and given by

$$\begin{aligned} u_N &= -A f(\rho) \\ f(\rho) &= \sqrt{\rho} \\ \rho &= \sum_{i \neq 0} \phi(R_i) \end{aligned} \quad (3.21)$$

where ϕ is a potential function, R_i labels the position of the neighbor i . The form of the function f mimics the result of tight-binding theory, in which the potential is interpreted as a sum of square of overlap integrals [52]. The core-core repulsion energy u_p is written as

$$u_p = \frac{1}{2} \sum_{i \neq 0} V(R_i) \quad (3.22)$$

where V is some core-core potential function. Now, considering first and second neighbors of a bulk atom in a b.c.c. lattice with unit cell of size a , we then have

$$\rho = 8\phi(\sqrt{3}a/2) + 6\phi(a) \quad (3.23)$$

$$u_p = 4V(\sqrt{3}a/2) + 3V(a) \quad (3.24)$$

For calculations with transition metal ions, Finnis [51] adopted for the attractive energy a quadratic cohesive potential

$$\begin{aligned} \phi(r) &= (r - d)^2, \quad r \leq d \\ &0, \quad r > d \end{aligned} \quad (3.25)$$

where d is a disposable parameter. For the pair-potential, V , Finnis adopted a quartic polynomial

$$\begin{aligned} V(r) &= (r - c)^2(c_0 + c_1r + c_2r^2), \quad r \leq c \\ &0, \quad r > c \end{aligned} \quad (3.26)$$

of which all constants are to be fit according to experimental data. This theory naturally introduces the effect of second nearest neighbors in the bonding energy of the atom. Once the potential functions are calculated by fitting experimental data, one can apply the theory to surface atoms by modifying equations 3.23 and 3.24.

The second problem of addressing the extent to which the electric field depends on local morphology of the surface is a more complicated one. The electric field influences the

kinetics of the on going reactions by altering their chemical activation energies, which is expressed in the Butler-Volmer equation with the inclusion of the exponential electrical term

$$i = i_0 \{ \exp[\beta n F \eta / RT] - \exp[-(1-\beta) n F \eta / RT] \} \quad (2.1)$$

which shows how the system deviates from the equilibrium kinetics. An important aspect is that the electrical term is decoupled from the chemical one incorporated in the constant i_0

$$i_0 \propto \exp(\Delta G^\ddagger / RT)$$

which supports the simple interpretation of competition between the electric and bonding terms in our simulation. At the electrochemical interface, fields are applied by establishing a gradient of electrical potential between the bulk metal and the bulk electrolyte. Classical electrostatics predicts that inside the metal, the electrical potential is constant throughout the bulk, and it changes in the vicinity of the surface. If this change in potential depends on the local morphology of the surface, the field established by the gradient will consequently vary throughout the surface.

Perhaps the best evidence for variations of perpendicular surface fields on atomic scale are the results of field ion microscopy (FIM), which is a technique to image surface atoms with which resolution of less than 1 nm can be achieved [53]. To image a sample with FIM, the specimen is prepared in the form of a sharp tip, to which a positive potential is applied to create fields of the order of 5×10^8 V/cm at the surface. Cooled gas near the surface is then ionized and accelerated towards an imaging screen. The ionization of the gas is most likely to happen where the local electrical field is highest, i.e. where the radius of the curvature of the tip is largest, so steps and kinks are more likely to ionize atoms than flat terraces.

Together with site dependent bonding energy, microscopic variations of the electric field on the electrochemical interface may contribute on determining the nature of active sites of dissolving metal surfaces. To the best of our knowledge, fundamental electrochemical studies have ignored this aspect. We intend to carry theoretical studies with which we could identify length scales of possible electric field variations, as well as the extent of their importance to metal dissolution when compared with other energy terms such as that of bonding.

3.4 Passivation

Passivation is one of the most important processes in the field of corrosion protection since the formation of a passive film can induce a high degree of corrosion resistance to a substrate that would otherwise corrode. It is well known that for many engineering metals and alloys, the passivation process is initiated by sub-monolayer adsorption of oxygen or hydroxide ions. For example, Frankenthal [37] showed that passivation of Fe-Cr alloys was completely reversible, demonstrating that it is controlled by an adsorption mechanism. Frankenthal concluded that only a fraction of a monolayer was necessary for passivation to occur, and that oxygen adsorption at surface active sites was the controlling process. We also note that passivation by oxygen adsorption is similar to the mechanism of corrosion inhibition by adsorption. Our theoretical simulations are readily modifiable for the study of such processes.

We therefore propose to investigate passivation by determining the effect of adsorption as a function of the type of surface site. The reversibility of this initial state of the passivation process [37] motivates the use of treatments developed to explain chemisorption phenomena of gases on metals [54]. In these treatments, the fraction of the exposed surface that is covered is determined by the pressure of the gas phase, the temperature of the substrate and the heat of adsorption. Since electrochemisorption of oxygen occurs preferentially at active sites, the binding energy of the ion can be easily calculated from parameters of the model and be interpreted, in a first approximation, as a parameter similar to the heat of adsorption. Relevant electrochemical quantities, such as electrode potential, may play thermodynamic roles as pressure does in the case of gas. Experimentally observed relationships of surface coverage as a function of temperature, such as the Temkin (linear) or Freundlich (logarithmic) isotherms [54], will be considered in trying to describe the relative dependence of surface site adsorption.

Using this approach we will address two aspects of this problem. First we will examine the effect on the dissolution current of adsorption of passivating ions (e.g. oxygen) at different surface sites. We then expect to have a better understanding of the efficiency of the passivation process by selecting the sites which give values of current decrease which are most representative of experimental data. Second, we will determine the relationship between the dissolution current and the fractional coverage of adsorbed species.

3.5 Dynamic Model of Dissolution Current

One important topic at which this research is aimed is the fundamental understanding of electrochemical noise. The study of fluctuations in potential or current has gained considerable interest in the field of electrochemistry, the motivation being that higher moments of measurable parameters could carry new information on the kinetic processes at the interface, which cannot be simply determined from phenomenological average values, such as the electrode current given by the Butler-Volmer equation (2.1).

Evidence for the fact that interface information can be obtained from noise measurements is given by the large amount of experimental results. Typically, fluctuations are measured on the current for constant electrical potential across the interface, on the potential for constant current, or on potential under open circuit conditions. Experimental work related to corrosion systems can be traced down to 1968 when Iverson [7] measured potential fluctuations between a platinum electrode and various working electrodes. It was then observed that the noise level decreased abruptly with the addition of an inhibitor to the electrolyte. Other authors have reported correlation between electrochemical noise and the corrosion process, and a trend of increasing power with increasing corrosion rate is commonly observed. To date, fluctuations have been observed in many other electrochemical systems including: metal dissolution, electrodeposition, pitting, and etching of semiconductors.

Noise due to initiation of pitting and breakdown of passive films have been studied by several authors [9,10]. Close to the pitting potential, a large increase in the power spectrum of the current noise at low frequencies is observed. This increase in noise power is reported to be due to the spontaneous breakdown event associated with relatively long time constants. Slow repassivation events also contribute to the low frequency spectrum. These systems are examples where initiation of corrosion can be monitored using noise techniques. Williams et. al. [16] have developed a stochastic model for the pitting process from which noise signals can be predicted.

Another source of noise is gas bubble evolution at the electrode [55]. The bubbles cover part of the exposed surface, increasing the impedance and the overpotential of the interface. Nucleation, growth and detachment of these bubbles induce fluctuation of the potential similar to those observed at passive film breakdown events. This noise has been

studied by different authors, and stochastic models have been proposed from which the power spectrum of the generated noise can be calculated.

Other interesting studies include: fluctuations in potential on electrocrystallization processes reported to be due to reaction steps leading to lattice formation [56,57]. Detection of change in corrosion mechanism from pitting to general corrosion by observation of fluctuations on potential [8]. Fluctuations in current ascribed to instabilities in passivation processes, at potentials close to the passivation potential [58,59].

In spite of the large amount of existent experimental data, not much theoretical work has been done in trying to establish a framework in which the origins of the fluctuations could be understood on a microscopic level. Our preliminary studies (section 2) [60] consider the dissolving surface under the fixed applied potential as a dynamic structure whose morphology changes due to ensemble fluctuations. These fluctuations are built naturally in the context of statistical thermodynamics, whose formalism is very much suited for this type of kinetic problem [61].

It is particular to driven dissolution systems that fluctuations on surface morphology are followed by fluctuations on the electrical current (under potentiostatic conditions), since the dynamics of the surface morphology is physically due to the removal of the atoms from the surface. In section 2 we showed that if the following equation of dissolution is considered,

$$i_+ = A \sum_q n(q,t) \exp(-\Delta E(q)/k_b T) \quad (2.3)$$

then ensemble fluctuations of the active sites (labeled by the index q) affect the current:

$$\frac{\partial i_+}{\partial t} = A \sum_q \frac{\partial n(q,t)}{\partial t} \exp(-\Delta E(q)/k_b T) \quad (2.4)$$

so we expect fluctuations in the current to be correlated with morphological changes of the surface. The level of these fluctuations and, consequently, their detectability are still to be investigated.

We propose to investigate further on this source of electrochemical noise by implementing features in our model with which we can introduce kinetic aspects in the simulation. Following the dynamic interpretation of the Monte Carlo method described by Binder [38], we can construct a time evolution of the dissolving interface in the following way. The surface can undergo a transition from configuration $\mathbf{x}$ to $\mathbf{x}'$ by dissolution of atoms labeled by (v) ($v = 1, 2, \dots, N$). Let the dissolution rate of each individual atom be r_v . The *instant* rate at which the surface dissolves is then

$$R = \sum_v r_v \quad (3.28)$$

It is natural to think of the dissolution process as having stochastic kinetics. We therefore assume the dissolution of one atom as a Poisson process, by considering that the surface atom v has a probability of not dissolving in a time t equal to

$$P_v(t) = e^{-r_v t} \quad (3.29)$$

The total probability that the surface is unchanged in a time t is then given by

$$P(t) = \prod_v e^{-r_v t} = e^{-\sum_v r_v t} = e^{-Rt} \quad (3.30)$$

and the probability that the first change in morphology occurs between t and $t+dt$ is

$$P'(t) = P(t) R dt = R e^{-Rt} dt \quad (3.31)$$

The time evolution of the system is generated by sampling time intervals between dissolution events from the distribution $R e^{-R\Delta t}$, which is done by setting $\Delta t = -\ln(\xi)/R$, where ξ is a random number. Notice that Δt will fluctuate not only due to the randomness of ξ , but also because the rate R will vary with time. Within each generated time interval, atoms are dissolved according to their probabilities of dissolution, which are derived from the ratio of dissolution rates as discussed in section 3.3.2. The total electrical current can, in this manner, be monitored throughout the simulation by counting the number of atoms dissolved and dividing by the generated time interval.

Although this model may require knowledge of activation energies for individual dissolution steps, it avoids the estimation of pre-exponential factors (eqns 3.11 and 3.13), since the probabilities are given by the ratios of dissolution rates, and the generated time intervals can always be normalized to fit experimental data.

4 - References

- 1 - R.B. Heimann in Crystals - Growth, Properties and Applications, vol 8, ed. J. Grabmaier, Springer-Verlag, New York (1982)
- 2 - Wieland, E., Wehrli, B., Stumm, W., Geochim. Cosmochim., 52, 1969, (1988)
- 3 - Wehrli, B., Wieland, E., Furrer, G., Aquatic Sciences, 52, 3, (1990)
- 4 - Wehrli, B., J. Colloid and Interf. Sci., 132, 230, (1989)
- 5 - Blum, A.E., Lasaga, A.C., Aquatic Surface Chemistry, W. Stumm, Eds, Wiley-Interscience, NY, (1987)
- 6 - Wagner, C., Traud, W., Z. Elektrochem., 44, 391, (1938)
- 7 - W.P. Iverson, J. Electrochem. Soc., 115 (1968) 617
- 8 - P.C. Searson and J.L. Dawson, J. Electrochem. Soc., 135 (1988) 1908
- 9 - C. Gabrielli, F. Huet, M. Keddam, and A. Macias, in Surfaces, Inhibition and Passivation, eds. R.J. Brodd and E. McCafferty, Electrochemical Society, Pennington, NJ (1986)
- 10 - T. Hagyard and W.B. Earl, J. Electrochem. Soc., 114 (1967) 694
- 11 - K. Hladky and J.L. Dawson, Corr. Sci., 22 (1981) 231
- 12 - U. Bertocci, J. Electrochem. Soc., 127 (1980) 1931
- 13 - U. Bertocci, J. Electrochem. Soc., 128 (1981) 520
- 14 - U. Bertocci and J. Kruger, Surface Science, 101 (1980) 608
- 15 - U. Bertocci, J.L. Mullen, and Y.X. Ye, in Passivity of Metals and Semiconductors, ed. M. Froment, p.229, Elsevier, (1983)
- 16 - D.E. Willimas, C. Westcott, and M. Fleischmann, J. Electrochem. Soc., 132 (1985) 1796
- 17 - V.A. Tyagai and N.B. Lukyachikova, Surface Science, 12 (1968) 331
- 18 - V.A. Tyagai, Elektrokhimiya, 3 (1967) 1331
- 19 - Brodd, R.J. and Leger, V.E., in Encyclopedia of Electrochemistry of the elements vol 5, ed. A.J. Bard, p. 2, Dekker, New York (1976)
- 20 - Allgaier, W. and Heusler, K.E., J. of App. Electrochem. 9, 155 (1979)
- 21 - Folleher, B. and Heusler, K.E., J Electroanal. Chem. 180, 77 (1984)

- 23 - Sieradzki, K. , Corderman, R. R., Shukla, K. and Newman, R. C.,
Philosoph ical Magazine A, vol 59, 4, 713 (1989)
- 24 - Kohli, C. S. and Ives, M. B., J. Crys. Growth 16, 123 (1972)
- 25 - Cheng, K.W. and Collier, A.W., J. Crys. Growth 84, 436 (1987)
- 22 - Bellingham, J., Phd Thesis, Physics Dept - MIT, (1988)
- 26 - Weeks, J.D. and Gilmer, G.H. in Adv. Chem. Phys. 40, 157, Wiley, New York
(1979)
- 27 - Beijeren, H. and Nolden, I. in Structure and Dynamics of Surfaces II,
eds. Schmmers W. and Blackenhagen P., Springer-Verlag (1987)
- 28 - Family, F. and Vicsek T., J. Phys. A 18, L75 (1985)
- 29 - Family, F. , Physica A, 168, 561 (1990)
- 30 - Thomas, T.R., Rough Surfaces, Longman, London, (1990)
- 31 - Human, H.J., Van Der Eerden, J.P., Jetten, L.A.M.J., Odekerken, J.G.M.,
J. Cryst. Growth, 51, 589 (1981)
- 32 - Guo, H., Grossmann, B., Grant, M. , Phys. Rev. Let., 64, 1262, (1990)
- 33 - Armar, J.G., Family, F., Phys. Rev. Let., 64, 543, (1990)
- 34 - Hwa, T., Kardar, M., Paczuski, M., Phys. Rev. Let., 66, 441, (1991)
- 35 - Phillips, R., Chrzan, D. C., Phys. Rev. Let., 67, 220, (1991)
- 36 - Furrer, G., Stumm, W., Geochim. Cosmochim., 50, 1847, (1986)
- 37 - Frankenthal, R.P., J. Electrochem. Soc., 115, 580 (1969)
- 38 - Binder, K. , Monte Carlo Methods in Statistical Physics, Springer-Verlag
Berlin, 1986
- 39 - Chan, C.K., Liang, N.Y., Phys. Rev. Lett., 67, 1122 (1991)
- 40 - Meakin, P., Sapoval, B., Phys. Rev. A, 43, 2993, (1991)
- 41 - Bates, J.B., Chu, Y.T., Stribling, W.T., Phys. Rev. Lett., 60, 627 (1988)
- 42 - Keddam, M., Takenouti, H., Electrochim. Acta., 33, 445 (1988)
- 43 - Nozières, P., Gallet, F., J. Phys. (Paris), 48, 353 (1987)
- 44 - Manne, S., Hansma, P.K., Massie, J., Elings, V.B., Gewirth, A.A.,
Science, 251, 183 (1991)
- 45 - Clark, J.T., Hampson, N.A., J. Electroanal. Chem., 26, 307 (1970)

- 46 - Brood, R.J., Leger, V.E., in Encyclopedia of Electrochemistry of the Elements, Vol 5, ed. A.J. Bard, p. 2, Dekker, New York (1976)
- 47 - Hush, N.S., Blackledge, J., J. Electroanal. Chem, 5, 420 (1963)
- 48 - Hush, N.S., Blackledge, J., J. Electroanal. Chem, 5, 435 (1963)
- 49 - Glasstone, S., Laidler, K.J., Eyring, H., The Theory of Rate Processes, McGraw-Hill, New York (1941)
- 50 - Blum, A., Lasaga, A., in Aquatic Surface Chemistry, ed. W. Stumm, John Wiley & Sons, New York (1987)
- 51 - Finnis, M.W., Sinclair, J.E., Phil. Mag. A, 50, 45 (1984)
- 52 - Aschcroft and Mermin, Solid State Theory, Saunders (1976)
- 53 - Prutton, M., Surface Physics, Oxford (1983)
- 54 - F.C. Tompkins, Chemisorption of Gases on Metals, Academic Press, London (1978)
- 55 - Gabrielli, C., Huet, F., Keddam, M. and Macias, A., in Surfaces, Inhibition and Passivation, eds. R.J. Brodd and E. McCafferty, p.507, Electrochemical Society, Princeton, NJ (1986)
- 56 - Fleischmann, M., Labram, M., Gabrielli, C. and Sattar, A., Surface Sci., 101, 583 (1980)
- 57 - Bindra, P., Fleischmann, M., Oldfield, J.W. and Singleton, D., Disc. Faraday Soc., 56, 180 (1974)
- 58 - Frank, U.F. and Weil, K., Z. Elektrochem., 56, 814 (1952)
- 59 - Frank, U.F. and Meunier, L. Z. Naturforshung, 8b, 396 (1953)
- 60 - Fernandes, M. , Master's Thesis, Materials Science Dept - MIT (1991)
- 61 - Keizer, J., Statistical Thermodynamics of Nonequilibrium Processes, SpringerVerlag 1987)
- 62 - Vetter, K.J., Electrochem. Acta, 16, 1923 (1971)

5 - Publications and Lectures

5.1 Publications

"Electrochemical Dissolution Noise: A Computer Simulation," S.M. Thesis, MIT, M. Fernandes, June 1991.

"Simulation of Metal Dissolution," M. Fernandes and R.M. Latanision, **J. Electrochemical Society**, in preparation.

5.2. Lectures

"Simulations of Metal Dissolution," M. Fernandes and R.M. Latanision, DOE Corrosion Contractors Meeting, 19 September 1992, (Brookhaven).

"Simulations of Metal Dissolution," M. Fernandes and R.M. Latanision, Electrochemical Society Meeting, 17 October 1991 (Phoenix, AZ).

"Simulations of Metal Dissolution," M. Fernandes and R.M. Latanision, Tri-Services Conference, 13 May 1992 (Plymouth, MA).

END

**DATE
FILMED**

8 / 7 / 92