9:

011633

1 OF 1

DOE/ER/45125--9

DE92 011633

STRUCTURE AND SHEAR RESPONSE OF LIPID MONOLAYERS

**Progress Report
for the period August 1, 1990 - July 31, 1991**

Pulak Dutta and John B. Ketterson

**Northwestern University
Evanston, IL 60208**

February 1992

prepared for

**THE U.S. DEPARTMENT OF ENERGY
Agreement no. DE-FG02-84ER45125**

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

CONTENTS

I.	Abstract	3
II.	Progress	
	A. X-ray diffraction studies of lipid monolayers.....	4
	B. Anisotropy in lipid monolayers.....	5
	C. Atomic force microscope studies of Langmuir-Blodgett films	5
III.	Proposed research	
	A. X-ray diffraction studies of lipid monolayers.....	7
	B. Shear response of lipid monolayers	7
	C. Studies of the structure of Langmuir-Blodgett films	8
IV.	Grant-supported Publications.....	9

removed

Reprints removed

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of its employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

I. Abstract

We have been studying lipid monolayers both on the surface of water and after transfer to solid substrates. On the surface of water, we have determined in detail the structure of heneicosanoic acid monolayers along a high-pressure isobar, and correlated this information with viscosity data. We have also determined the effect of ions in the subphase on acid monolayer structure (as a function of pH). We have studied capillary waves on monolayer-covered water surfaces, and we find that these monolayers can be quite anisotropic in some phases, so that the monolayer 'pressure' is not always a meaningful quantity. Using atomic force microscopy, we have seen 'islands' in Langmuir-Blodgett monolayers without the need for a dye, plus features that are not visible using fluorescence microscopy.

During the next year, we propose to investigate the role of head-head interactions further by performing X-ray diffraction studies of heneicosanol monolayers and mixed acid-alcohol monolayers. We also propose to study the structure of LB films transferred from different monolayer phases, using X-ray diffraction. Finally, we will use a shear balance of our design to study the mechanical properties of the different phases of heneicosanoic acid monolayers.

II. Progress

A. X-ray diffraction studies

We followed up on our study of the phase diagram of a fatty acid monolayer, published during the previous year [1], with two X-ray studies of monolayers on the surface of water.

First, we studied the effect of pH on Langmuir monolayer structure [2]. In the presence of calcium ions in the subphase, we varied the pH from 2 to 11 and studied the monolayers using isotherms and X-ray diffraction. Since the results are described in the reprint provided with this report, we will give only a brief summary here. It has long been known from isotherm studies [3] that, in the presence of calcium ions, the monolayer is 'condensed' by increasing pH at zero pressure. We confirmed this with microscopic (diffraction) data, and also found that the compression of the unit cell is primarily uniaxial. A related effect is that, as the pH increases, the chain tilt at zero pressure decreases. As a result, the transitions seen in the isotherms are pulled down to lower pressures, until the isotherm has the featureless 'salt' form and the high-pressure structure is seen at all pressures. At very high pH (~ 11), however, a completely new structure is observed, which has $b/a \approx 2$.

Second, we looked in detail at the well-known 'superliquid' region of Langmuir monolayers [4]. Again, since the results are described in an attached preprint, we will give only a brief summary here. One of the features of the fatty acid isotherm (known today to indicate the onset of chain tilt) goes from a 'kink' to a 'flat section' and back to a 'kink' again as a function of temperature, within a few degrees C. It has been known for some time [5] that the monolayer viscosity behaves anomalously in this region; this gave rise to the 'superliquid' label. Using isotherm and X-ray diffraction studies, we found a quite complex phase diagram in

this region. At high pressures, the phase sequence as a function of temperature is the same as in lamellar paraffins: the monolayer goes from a distorted-hexagonal 'crystal' structure to a hexagonal 'rotator-II' structure, via an intermediate 'rotator-I' structure. What is more, the peak widths are larger in the rotator-I region than in any of the neighboring phases; this correlates with the anomalous viscosity minimum previously seen in this region [5].

B. Anisotropy in lipid monolayers

Lipid monolayers are almost compressed uniaxially; now that our results show that these monolayers may be solid, the appropriateness of such a mode of compression, and the meaning of 'pressure' in uniaxially compressed solids, may be called into question. We looked at capillary wave propagation parallel and perpendicular to the compression direction, using a fiber-optic probe of our own design [6]. We found that the monolayers can be anisotropic, as suspected, but only in certain low-temperature phases (the phases labelled A and B in Ref. 1). When such anisotropy develops, it decays with time but does not vanish for several hours. In the higher-temperature phases, however, no anisotropy is created by uniaxial compression.

C. Atomic force microscopy (AFM)

We have performed AFM studies of monolayers transferred to glass substrates using the Langmuir-Blodgett (LB) technique. These films were transferred from floating monolayers in a two-phase coexistence region. 'Islands' have previously been reported both in the monolayers on water and in the transferred monolayers, but these were seen by adding an impurity dye and using a fluorescence microscope. We see such islands using AFM without the need for a dye. We also see added details within the islands, and in the less-dense phase that

surrounds them, that have not been seen with fluorescence microscopy.

We have made a detailed study of transferred islands as a function of parameters such as the surface pressure and temperature during transfer, and the presence or absence of dyes (the dye-containing films were also examined under a fluorescence microscope). Variations of film thickness were studied; we find that each 'island' is rimmed by a thicker 'atoll' whose origin is not yet understood.

1. B. Lin, M.C. Shih, T. M. Bohanon, G.E. Ice and P. Dutta, *Phys. Rev. Lett.* **65**, 191 (1990)
2. M.C. Shih, T.M. Bohanon, J.M. Mikrut, P. Zschack and P. Dutta, *J. Chem. Phys.*, **96**, 1556 (1992)
3. J.A. Spink and J.V. Sanders, *Trans. Faraday Soc.* **51**, 1154 (1955)
4. M.C. Shih, T.M. Bohanon, J.M. Mikrut, P. Zschack and P. Dutta, *Phys. Rev. A*, to be published (4/15/92 issue)
5. L.E. Copeland, W.D. Harkins and G.E. Boyd, *J. Chem Phys.* **10**, 357 (1942)
6. T.M. Bohanon, J.M. Mikrut, B.M. Abraham, J.B. Ketterson and P. Dutta, *Revs. Sci. Instrum.* **62**, 2959 (1991)

IV. Grant-supported publications (1991-)

"Measurement of contact angle relaxation during the deposition of Langmuir-Blodgett films of cadmium stearate and valinomycin", J.B. Peng, S. He, P. Dutta and J.B. Ketterson, *Thin Solid Films* **202**, 351 (1991)

"Phase transitions in lipid monolayers on water: new light on an old problem", P. Dutta, in "Phase Transitions in Surface Films 2", edited by H. Taub, G. Torzo, H.J. Lauter and S.C. Fain (Plenum Publishing Co., New York, 1991) pg. 183

"Studies of structures and phase transitions of Langmuir monolayers using synchrotron radiation", P. Dutta, SPIE Proceedings Vol. 1550 (1991) p. 134

"Pressure and pH dependence of the structure of a fatty acid monolayer with calcium ions in the subphase", M.C. Shih, T.M. Bohanon, J.M. Mikrut, P. Zschack and P. Dutta, *J. Chem. Phys.*, **96**, 1556 (1992)

"X-ray diffraction studies of fatty acid monolayers on the surface of water", M.C. Shih, T.M. Bohanon, J.M. Mikrut, P. Zschack and P. Dutta, in "Surface X-ray and Neutron Scattering", Springer Proceedings in Physics Vol. 61, edited by I.K. Robinson and H. Zabel (Springer-Verlag, Berlin, 1992) p. 151

"An apparatus with an elastic barrier for radial compression of liquid supported monolayers", T.M. Bohanon, J.M. Mikrut, B.M. Abraham, J.B. Ketterson, S. Jacobson, L. Flosenzier, J. Torkelson and P. Dutta, *Revs. Sci. Instrum.* **63**, 1822 (1992)

"X-ray diffraction study of the superliquid region of the phase diagram of a Langmuir monolayer", M.C. Shih, T.M. Bohanon, J.M. Mikrut, P. Zschack and P. Dutta, *Phys. Rev. A*, to be published (4/15/92 issue)

END

DATE
FILMED

6/12/92