CATALYST DISPERSION AND ACTIVITY UNDER CONDITIONS OF TEMPERATURE-STAGED LIQUEFACTION

Technical Progress Report for the Period
July to September 1991

by

Alan Davis, H.H. Schobert, G.D. Mitchell

and L. Artok

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PENNSSTATE

Energy & Fuels Research Center

(814) 865-6544

Pennsylvania State University
University Park, PA 16802

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. References herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

Two coals, a Texas subbituminous (lignite) and a Utah high volatile C bituminous, were used to examine the effects of solvent swelling pretreatment and catalyst impregnation on conversion behavior at 275°C, representative of the first, low-temperature stage in a temperature-staged liquefaction reaction. Ferrous sulfate, iron pentacarbonyl, ammonium tetrathiomolybdate, and molybdenum hexacarbonyl were used as catalyst precursors. Without swelling pretreatment, impregnation of both coals increased conversion, mainly through increased yields of preasphaltenes. Methanol, tetrahydrofuran, tetrabutylammonium hydroxide, and pyridine were used as swelling agents. In the absence of catalyst, swelling the subbituminous coal before reaction improves conversion by enhancing oil and gas yields; the effectiveness of the solvents in enhancing conversion is in the same order as their swelling ratios. Swelling with methanol or pyridine has little effect on reaction of the bituminous coal, but both tetrahydrofuran and tetrabutylammonium hydroxide treatments increase conversion as a result of higher preasphaltene yields. The combined effect of catalyst addition and swelling enhances conversion, as much as two-fold, of the subbituminous coal and increases yields of all products. On the other hand, little benefit was obtained by combining catalyst addition and swelling for the bituminous coal, though it is possible to effect changes in the relative amounts of the various products. Tetrabutylammonium hydroxide not removed from the coal after pretreatment appears to decompose to the good solvent tributylamine, suggesting the possibility of using swelling agents as "solvent precursors," first swelling the coal and then

thermally decomposing to a strong solvent that is emplaced inside the coal. The action of iron pentacarbonyl is sensitive to the reactive gas atmosphere used; in hydrogen it decomposes to an oxide that mainly facilitates hydrogenation of the heavy products to lighter oils, whereas in hydrogen sulfide / hydrogen mixtures the iron pentacarbonyl is sulfided and mainly facilitates depolymerization of the coal to heavy products. This finding suggests the possibility of tailoring the behavior of the catalyst by appropriate selection of catalyst precursor and reactive atmosphere.

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	iii
PROGRAM OBJECTIVES	1
PROGRAM OUTLINE	1
Catalyst Transformation	1
Catalysts and Their Dispersion	2
Coal Pretreatment	3
Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs	4
DESCRIPTION OF TECHNICAL PROGRESS	6
1. THE EFFECT OF PRESWELLING AND CATALYST PRECURSOR ON LIQUEFACTION OF COALS	6
SWELLING PRETREATMENT OF COALS FOR IMPROVED CATALYTIC LIQUEFACTION	7
1.1. <u>Introduction</u>	7
1.2. <u>Experimental</u>	10
1.2.1. Coal Sampling and Initial Swelling Ratio Determination	10
1.2.2. Swelling of Coals Prior to Liquefaction	12
1.2.3. Catalyst Preparation and Testing	12
1.2.4. Impregnation of Swollen and Unswollen Coals with Catalyst Precursors	14
1.2.5. Examination of Catalyst Dispersion	15
1.2.6. Liquefaction Reactions and Product Work-up	16
1.3. <u>Results and Discussion</u>	18
1.3.1. Swelling of Coals	18
1.3.2. Comparison of Molybdenum and Iron Catalyst Precursors for Pretreatment	20
1.3.3. The Effect of Preswelling on Non-catalytic Liquefaction	29
1.3.4. Combined Effects of Swelling and Catalyst Impregnation	33
1.4. <u>Conclusions</u>	38
1.5. <u>Acknowledgements</u>	42
References	43

PROGRAM OBJECTIVES

The general objectives of this research are 1) to investigate the use of highly dispersed catalysts for the pretreatment of coal by mild hydrogenation, 2) to identify the active forms of the catalysts under reaction conditions and 3) to clarify the mechanisms of catalysis. The ultimate objective is to ascertain if mild catalytic hydrogenation resulting in very limited or no coal solubilization is an advantageous pretreatment for the transformation of coal into transportable fuels. The experimental program will focus upon the development of effective methods of impregnating coal with catalysts, evaluating the conditions under which the catalysts are most active and establishing the relative impact of improved impregnation on conversion and product distributions obtained from coal hydrogenation.

PROGRAM OUTLINE

Catalyst Transformation

Four catalyst materials have been selected for this investigation: ammonium tetrathiomolybdate, ferrous sulfate, molybdenum hexacarbonyl, and iron pentacarbonyl. Insofar as it is possible, these catalysts will be evaluated by TGA in order to determine 1) the temperature at which a chemical change occurs in the catalyst precursor, 2) the holding time at that temperature needed to reach completion of the transformation, and 3) and effects of heating rate on catalyst precursor transformation. Experiments will be performed for each catalyst for a matrix of conditions, as follows: 1) three heating rates: 5°, 50°, and about 125°C/min; 2)

three final temperatures: 275°, 350°, and 425°C; 3) two atmospheres, namely nitrogen and hydrogen; and 4) one "soak time" at temperature (1 h). Also, in order to define the heating regimes over which both catalysts and coals decompose, each of the two test coals will be evaluated in the TGA under the same reaction conditions employed with the catalysts.

Each of the catalyst precursors will be tested in 25 Ml microautoclaves (tubing bombs) in order to prepare larger quantities of the transformed materials for subsequent characterization. The time-temperature regimes used in these experiments will be selected based on results from the TGA study. Three atmospheres will be used: 1) nitrogen, 2) hydrogen, and 3) 95:5 hydrogen:hydrogen sulfide. In each of these experiments the tubing bomb will be pressurized to 1000 psi (cold).

Catalysts and Their Dispersion

The purpose of this portion of the research effort is to investigate methods of impregnating coal with catalysts prior to liquefaction. A variety of techniques that are best suited for a particular catalyst will be explored. Those planned include:

- a) using the ammonium tetrathiomolybdate or ferrous sulfate in aqueous solution; the coals will be slurried with the solution of catalyst precursor and then freeze-dried;
- b) these same precursors will be applied to coal in solvents that are known to swell coal structures; THF, pyridine, methanol and tetrabutylammonium hydroxide. However, the catalyst materials must be either soluble or form a fairly stable suspension in the appropriate solvent in order to promote access of catalyst to interior surfaces of the coal;
- c) iron pentacarbonyl and molybdenum hexacarbonyl will be applied to coal in hydrocarbon or other organic solvents that may promote coal swelling;

- d) ion exchange of iron, as ferrous sulfate, onto the lignite selected for this project will also be investigated.

With some basic information with respect to solvent and catalyst interactions, both individual large particles and fine particulate samples of each coal will be impregnated or ion-exchanged with the catalyst, and the dried sample prepared and observed under the SEM to determine the extent of impregnation and dispersion of the catalyst.

Coal Pretreatment

Two coals, a lignite and an hvCb, will be selected from the Penn State Sample Bank in consultation with DOE. Each coal will possess high vitrinite and low sulfur contents and ash yields, and will have been thoroughly characterized by proximate and ultimate analyses, maceral and reflectance analyses, as well as major and trace elements.

The principal objective of this work is to explore the influences of catalyst presence, dispersion and chemistry on coal pretreatment. All experiments will be carried out in 25 Ml microautoclave reactors, under 1000 psi (cold) pressure and using a nominal 5 g of coal and 5 g of vehicle. The time-temperature regimes will be defined on the basis of results obtained from the catalyst transformation investigations.

Temperature-staged liquefaction consists of two distinct steps, the low-temperature pretreatment and the high-temperature liquefaction reaction. The main focus of this work is on pretreatment, and therefore most of the experiments will be carried out in the range of 275°-350°C. In order to assure that the pretreatment stage has been effective in converting the starting coal into an "active coal" intermediate, a limited number of

experiments will be performed incorporating the second, high-temperature stage (425°C) as well. The gas atmosphere will be hydrogen. If tests from the catalyst transformation work are encouraging, additional experiments will be performed in 95:5 H₂:H₂S atmospheres.

Experiments will be run without catalyst to obtain baseline data and with each of the four catalyst precursors. The level of catalyst loading will be chosen to ensure that the amount of metal left in the residue is detectable by the planned characterization techniques. Also, catalyst loading will be adjusted so that the same loading on a gram-atom basis is achieved for the iron and molybdenum. Furthermore, the experiments will be run with and without a hydrogen-donor vehicle. It is planned to use phenanthrene as a non-donor vehicle and dihydrophenanthrene as a donor vehicle.

Following liquefaction, a variety of conventional techniques will be used to characterize gaseous, liquid and solid products. Gases will be routinely analyzed by gas chromatography. Oils and asphaltenes will be routinely analyzed by GC, GC/MS, and ¹H NMR, and by FTIR and ¹³C (solution) NMR for selected samples. Selected samples of the solid residue will be characterized by DRIFT, ¹³C (solid) NMR and optical and electron optical microscopy.

Evaluation of Impregnated Coals and Residual Materials from Other DOE Programs

Impregnated coals and liquefaction residues will be solicited from DOE and its contractors for microscopic study of materials generated in larger scale experiments than ours, and through other novel approaches to

hydrogenation. Samples also will be sought from projects that are developing unique techniques for the impregnation of catalyst into coals for liquefaction. It is expected that many of these samples will come from PETC and the Advanced Research program to assess the degree of catalyst dispersal and to assess the relative extent of hydrogenation and condensation reactions.

DESCRIPTION OF TECHNICAL PROGRESS

1. THE EFFECT OF PRESWELLING AND CATALYST PRECURSOR ON LIQUEFACTION OF COALS

The greater part of the experimental work concerning catalyst transformation and the coal pretreatment with its associated product work-up has been completed during this reporting period. Another major activity has been assembling and reducing the data for the final project report. To facilitate expeditious technology transfer, we have also begun the preparation of several manuscripts for publication in the peer-reviewed professional literature. The draft of one of these papers is incorporated in this report. This paper has been accepted for publication in *Fuel* pending the incorporation of minor changes.

A second paper, "Transformation of Impregnated Ferrous Sulfate to Pyrrhotite Under Liquefaction Conditions" resulting directly from the results of this project, is in an advanced state of preparation. It will be submitted to *Fuel Processing Technology*. A third manuscript entitled "Swelling Pretreatment of Coals for Catalytic Temperature-Staged Liquefaction" deals with the results of experiments in which the effects of pretreatment upon a second, higher temperature, stage are explored. Upon completion this manuscript will be submitted to *Energy & Fuels*.

The modified draft of the first of these papers follows:

SWELLING PRETREATMENT OF COALS FOR IMPROVED CATALYTIC LIQUEFACTION

1.1 Introduction

It has been known for some time that improvements in catalytic liquefaction can be obtained by having the catalyst or catalyst precursor (i.e., a compound that would decompose to an active catalyst at reaction temperature) impregnated into the coal rather than simply mixed with the coal as a powder.¹ Having catalyst particles present at the sites of bond cleavage in the coal structure facilitates hydrogenation; away from the vicinity of the catalyst both carbonization and cracking to gases will be favored.² Hence both the total liquid yield and product quality improve as the extent of catalyst dispersion improves. The use of red mud and supported cobalt-molybdenum catalysts in liquefaction of bituminous coals was effective only when there was a rapid plasticizing of the coal and generation of hydrogen donor species, because these catalysts could not be effectively dispersed through the coal.³ Prior work at this university has demonstrated the effectiveness of impregnating a water-soluble sulfided ammonium molybdate into coal before liquefaction.^{4,5} Impregnated ammonium thiomolybdates were more effective catalysts for liquefaction and hydrodesulfurization of Spanish lignite than admixed molybdenum disulfide, a fact attributed to the superior dispersion of the soluble molybdenum salts relative to that obtained from the insoluble disulfide.⁶

Hawk and Hiteshue have cited results in which ammonium molybdate was found effective for liquefaction of Wyoming subbituminous coal regardless of whether the salt had been dispersed in aqueous solution or not.² It

seemed that in this case the organic liquefaction solvent could itself act as the vehicle for impregnating the catalyst, even though the salt would be essentially insoluble in the solvent. The dispersal of the catalyst by the vehicle has been invoked as a reason for the improved catalyst activity (though it must be recognized that solvent-catalyst interactions may also be an important factor). The dispersal of metal halide catalysts was achieved more effectively with organic solvents, methanol and acetone, than with aqueous solutions.⁷ A further approach to improve effectiveness of catalyst dispersion involves the use of metal salts of organic compounds or organometallic compounds. Thus metal naphthenates, which would be oil-soluble, were found to be very effective catalysts even at quite low (e.g., 0.01%) metal loadings.² Iron pentacarbonyl, which is soluble in organic media, is considered readily to penetrate the pore structure of coals and decompose to finely dispersed metallic iron or iron sulfide.⁸⁻¹⁰

Besides affecting catalyst behavior by dispersion, the activity of a catalyst may also vary, depending on structural modification of the coal. By modifying the structure of coal, the hydrogenation and dissolution activity of the catalyst can be promoted, because the weakened structure could be more susceptible to hydrogenation and depolymerization reactions. One method to modify coal structure is solvent swelling. The coal network can be swollen using appropriate solvents, leading to expansion of the pores. The swelling may facilitate impregnation of catalysts or catalyst precursors and diffusion of reagents to the reactive sites of coal. Therefore, it can be presumed that swelling as a pretreatment operation may increase conversion and quality of yield obtained from liquefaction.

Rincon and Cruz found that the conversion of a Colombian coal increased when it was swollen with tetrahydrofuran (THF).¹¹ Joseph determined a direct correlation between the extent of preswelling and the conversion of coal under liquefaction conditions.¹² Baldwin and co-workers also confirmed the beneficial effect of solvent swelling on coal liquefaction by obtaining better yield quality for the THF-swollen Illinois #6 coal.¹³

Temperature-staging of liquefaction involves reaction at two temperatures, an initial low-temperature (275-350°C) stage, followed by further reaction at higher temperature (375-450°C). The first, low-temperature stage is sometimes considered to be a pretreatment, since most of the desirable liquid products are still formed in the higher temperature stage. This strategy is known to improve net conversion to liquids, relative to operation at a single temperature, and selectively improves the yield of oils at the expense of asphaltenes without an attendant increase in gas production.¹⁴ During the low-temperature stage a partial depolymerization of the coal structure could increase the amount of extractable liquids and the coal fluidity.¹⁵ Weaker bonds might be broken and stabilized by hydrogen transfer at low temperature, reducing the potential for retrogressive condensation reactions at higher temperature. Thus effective hydrogenation at the mild reaction conditions of the first stage may minimize condensation reactions. In the case of low-rank coals, improvement in conversion to soluble products is also aided by the loss of carboxyl groups, but without formation of crosslinks.¹⁶ The combination of a low-temperature catalytic liquefaction step followed by a higher temperature catalytic reaction significantly improved product selectivity.

concomitant with attaining the highest conversion.¹⁷ Although the use of a catalytic low-severity first stage, using an impregnated molybdenum catalyst, provided processing advantages relative to single-stage reactions, few chemically significant changes were detected in the residual materials.¹⁸

In the present paper, we report results of a study using various types of iron and molybdenum catalyst precursors for coal liquefaction. The study involved an examination of the effects of impregnation of the catalyst onto the coal, the effects of swelling the coal prior to reaction, and the combined effects of swelling and catalyst impregnation. The focus of this work was on improvements to be obtained in the first, low-temperature (or pretreatment) stage; consequently all results reported in this paper are for reactions at a pretreatment temperature of 275°C.

1.2. Experimental

1.2.1. Coal Sampling and Initial Swelling Ratio Determination

Samples of Blind Canyon high volatile bituminous coal (PSOC-1503 and DECS-6) and Big Brown Texas lignite/subbituminous (PSOC-1444 and DECS-1) collected at different dates were used for this work. The Texas sample DECS-1 has a rank which lies close to the lignite/subbituminous C boundary, and other samples collected from the same vicinity, such as PSOC-1444, have a reported rank of lignite. The origin and analyses of the coals are given in Table 1. The coals were ground without drying to minus 60 mesh and stored under a nitrogen atmosphere. One gram of air-dried coal (PSOC-1444 and PSOC-1503) was placed in a 15 mL conical graduated screw-top centrifuge

Table 1. Characteristics of coals

Sample No.	PSOC-1444	PSOC-1503	DECS-1	DECS-6
Seam	Unnamed	Blind Canyon	Bottom	Blind Canyon
County	Freestone	Emery	Freestone	Emery
State	Texas	Utah	Texas	Utah
Province	Gulf	Rocky Mt.	Gulf	Rocky Mt.
Sampling Date	3/30/85	10/01/85	12/11/89	6/07/90
ASTM rank class	lignite	hVcb	sub C	hVBb
Moisture Content % wt	31.91	10.35	30.00	4.73
Min. Matter % wt (dry)	19.02	4.36	17.97	6.67
<u>Elem. Comp. (% dmmf)</u>				
C	76.21	80.80	76.13	81.72
H	4.71	6.12	5.54	6.22
N	1.42	1.55	1.5	1.56
S (org)	1.36	0.54	1.05	0.40
O (diff)	16.29	10.58	15.78	10.10

tube and centrifuged at 2900 rpm for 10 minutes. The height of the coal in the tube was recorded in mL/g. Twelve mL of solvent (methanol, pyridine, tetrahydrofuran, or tetrabutylammonium hydroxide) was added to the coal in two increments. The first 6 mL was combined with the coal and the mixture was stirred carefully until all the coal particles were wetted, then the remaining solvent was added and the tube was sealed with a cap. After a period of time (6-30h), the tube was centrifuged again at 2900 rpm for 10 min and the height was recorded. The volumetric swelling ratio is defined as $Q = h_2/h_1$, where h_1 = height of unswollen coal and h_2 = height of swollen coal. (It should be noted that the solvent swelling studies were performed

on the older, PSOC coals, while the reactivity experiments, discussed below, were performed using newer, DECS samples.)

1.2.2. Swelling of Coals Prior to Liquefaction

The coal samples (DECS-1 and DECS-6) were swollen using methanol, pyridine, THF and 10% tetrabutylammonium hydroxide (TBAH) solution (1:1 (w/w) ratio water:methanol mixture). The coal samples, which were predried at 110°C in vacuum, were mixed with the swelling reagent to give approximately a solvent-to-coal ratio of 3:1 and were stirred for 6 hours under nitrogen. The solvent was removed and dried at 50°C in vacuum. In the case of pyridine, the sample was dried at 100°C in vacuum in an attempt to remove pyridine completely. Based on the increased nitrogen content of the samples after pyridine treatment, the pyridine incorporation after drying was in the range of 2 - 10%. In the case of TBAH, a TBAH solution was added to undried coal and only methanol and water of the mixture were removed, so that TBAH was retained in the swollen coal matrix.

1.2.3. Catalyst Preparation and Testing

Ammonium tetrathiomolybdate, $(\text{NH}_4)_2\text{MoS}_4$ (ATTM), was synthesized in our laboratory following the procedure of Naumann.¹⁹ Briefly, 20 g ammonium heptamolybdate and 20 mL ammonium hydroxide are added to 100 mL deionized water and cooled to ~5°C in an ice bath. H_2S is bubbled through the solution until an initial yellow precipitate turns red; the flow is continued for an additional 30 minutes. The precipitate is filtered, washed with ethanol, and dried in vacuum at room temperature. Molybdenum trisulfide was prepared by acidifying an aqueous solution of ATTM with

formic acid, followed by washing and drying the precipitate at 110°C in a vacuum oven. Ferrous sulfate, molybdenum hexacarbonyl, and iron pentacarbonyl were purchased as reagent-grade chemicals and used without further treatment.

Thermogravimetric analysis of ATTM was performed using a Perkin Elmer model TGA-7 thermal analyzer at a heating rate of 20°C/min in nitrogen. Sulfur analyses were performed by the Penn State Materials Characterization Laboratory using a Leco iodimetric titration sulfur analyzer and in the Penn State Combustion Laboratory using a Leco Model SC-132 sulfur analyzer. Carbon, hydrogen, and nitrogen analyses were performed using a Leco Model CHN-600 elemental analyzer. Molybdenum, iron and water (by the Karl Fisher method) analyses were performed by Galbraith Laboratories, Inc. Elemental values and water content of synthesized molybdenum compounds are given in Table 2.

Table 2. Elemental analysis of ATTM, MoS_3 and the product obtained from microautoclave reaction of ATTM at 7MPa psi (cold) hydrogen gas at a temperature of 275°C

Catalyst	%N	%H	%Mo	%S	%H ₂ O	nS:nMo
ATTM	10.81	3.10	37.01	49.15	ND	3.98
MoS_3	ND	ND	44.45	50.50	1.39	3.41
HATTM*	3.26	1.40	49.74	39.40	6.36	2.38

ND: Not determined

*Reacted ATTM in 7 MPa (cold) H_2 at 275°C.

Catalyst precursors were reacted in a microautoclave at 7 MPa (cold) H_2 or $\text{H}_2\text{S}:\text{H}_2$ mixtures at 275°C for one hour. In experiments with ATTM and ferrous sulfate, a 5:95 ratio of $\text{H}_2\text{S}:\text{H}_2$ was used; for molybdenum

hexacarbonyl the ratio was 13.6:86.4, and for iron pentacarbonyl, 18:72. These ratios were chosen in order to maintain a constant sulfur:metal ratio of 2.5 in the reactions. X-ray diffraction measurement of the products (XRD) were made using Cu-K α radiation with Rigaku equipment and operated at 40 kV and 20 mA.

1.2.4. Impregnation of Swollen and Unswollen Coals with Catalyst Precursors

The catalyst precursor was loaded onto the coal in an amount based on 1% molybdenum or 0.59% iron (as the metal, not the metal compound) on a dry ash free (daf) basis regardless of whether the coal had been swollen or not. Unswollen coals were impregnated with a water solution of ATTM, ferrous sulfate or suspension of molybdenum trisulfide and with a pentane solution of Fe(CO)₅ and Mo(CO)₆. The pentane was removed from carbonyl-impregnated coals by treatment in vacuum at room temperature for 10 minutes. Because of the volatility of carbonyls, the possibility exists that a portion of the carbonyl originally added may have been removed subsequently during the drying.

In the case of swollen coal, the swelling reagent (except TBAH) was removed in vacuum at room temperature. While the coal was still wet with swelling reagent, enough ATTM solution (which had been prepared by dissolving ATTM in 1:1 (v/v) ratio methanol:water mixture) to give solution-to-coal ratio of 1:1 was added to coal and stirred for 30 min. In the case of TBAH, ATTM was dissolved in a 10% TBAH solution of a 1:1 ratio (w/w) water:methanol mixture; then this solution was added to undried coal and stirred for 6 hours in order to give enough time for the swelling of

coal under nitrogen. After stirring, excess solvent was removed at room temperature in vacuum while it was continuously being stirred. Finally, vacuum drying was applied at 50°C for the coals swollen with methanol, THF or TBAH, or at 100°C for pyridine-swollen coal. TBAH was allowed to remain in the coal. When carbonyl compounds were used as catalyst precursor, THF and methanol were removed in vacuum at 50°C, and pyridine was removed in vacuum at 100°C prior to impregnation with pentane solution. Again in the case of TBAH, any residual TBAH was allowed to retain in coal.

The TBAH content of samples, whether catalyst-impregnated or not, was calculated from the increase of the nitrogen content of the TBAH-treated material relative to that of the untreated coals.

1.2.5. Examination of Catalyst Dispersion

To establish the physical relationship between catalysts and coal surfaces following impregnation, the interfaces were studied by scanning electron microscopy (SEM), to determine whether catalyst materials are deeply impregnated into the coal structure or whether they form only surface dispersions. Two types of samples were prepared from the Texas lignite (DECS-1 and PSOC-1444) and Blind Canyon bituminous coal (DECS-6): particulate (-60 mesh) samples, and single particles of about 5x20 mm embedded in plastic and polished to expose the bedding plane structures of the coal. The particulate samples were impregnated with catalyst or solvent swollen, or both, as described above, and were coated with gold for observation with an ISI model SX-40A SEM. Ferrous sulfate and ATTM catalysts were impregnated into methanol- and THF-swollen coals and moist

coals. An energy dispersive spectrometer (EDS) was used for qualitative analysis of elements greater in atomic number than sodium. The single-particle samples were stored under high humidity or were soaked in methanol for 48 h. Without allowing the polished surface to dry, ferrous sulfate (~1 mg) or ATTM (~0.5 mg) in the appropriate solvent (i.e., water or methanol) was applied in drops to the surface. Samples were then dried in vacuum at 25°C for 48 h and coated with carbon for SEM examination.

1.2.6. Liquefaction Reactions and Product Work-up

The liquefaction reactions were performed in horizontal microautoclave reactors (tubing bombs) of nominal 25 mL capacity. The procedure was the same for both preswollen and unswollen coals and also the same whether they had been impregnated with a catalyst or not.

Five grams of each prepared coal sample and five grams of phenanthrene were placed in the reactor. After mixing the contents with a spatula, the reactor was sealed, pressurized to 7 MPa with nitrogen and checked for leaks. The depressurized reactor was purged with hydrogen twice. Subsequently, the reactors were pressurized to 7 MPa (at room temperature) with hydrogen or $\text{H}_2\text{S}:\text{H}_2$ (5:95) and were attached to a fluidized sand bath which was heated to 283°C. Immediately after the reactors were placed in the sand bath, the thermostat was reset to 275°C, which was the desired pretreatment temperature. The reactors attained a temperature of 275°C in about 30 seconds. The reaction time was 30 minutes. During this period, the reactors were oscillated through an amplitude of 2 cm at 350 cycles/min. All the pretreatment experiments were done in duplicate. For

experiments in these reaction systems we have determined, in a collateral study on bituminous coal liquefaction, that the relative standard deviation (i.e., the standard deviation expressed as a percentage of the mean) of conversion results is 7-12% for six sets of results obtained by three independent experimenters each performing duplicate tests. Relative standard deviations for asphaltene yields are typically 12 - 13%.

At the end of the reaction, the reactors were rapidly quenched to room temperature by immersion in cold water. After venting the gas, the contents of each reactor were quantitatively washed into a tared ceramic thimble using toluene and Soxhlet-extracted with toluene under nitrogen until the solvent appeared colorless. The toluene extract was concentrated to 10-20 mL by rotary evaporation. The extract was diluted with 400 mL of hexane. The mixture was stirred for 1 h and asphaltenes were allowed to settle overnight and separated with a 0.45 micron filter. The filtrate, containing hexane-solubles, was treated by rotary evaporation to remove the hexane. Toluene-insolubles were Soxhlet-extracted with THF to separate preasphaltenes and the solid residue under a nitrogen atmosphere. THF was removed from the extract by rotary evaporation. Preasphaltenes, asphaltenes and residue were dried overnight in vacuum at 110°C. The conversion was calculated by subtracting the residue weight (corrected as appropriate for the weight of added catalyst) from the weight of coal and dividing by the daf weight of the coal. It was assumed that in the liquefaction system the catalyst precursors transformed to the same materials as they did in reactions in the absence of coal in hydrogen or $\text{H}_2\text{S}:\text{H}_2$ at 275°C (Table 2 and 3).

Table 3. Elemental analysis of products obtained from microautoclave reaction of Mo(CO)_6 and Fe(CO)_5 at 7MPa of H_2 and $\text{H}_2\text{S:H}_2$ (5:95) at 275°C

Catalyst Precursor	Reaction Gas	%Mo	%Fe	%S	%C
Mo(CO)_6	H_2	40.77	—	—	24.50
Mo(CO)_6	$\text{H}_2\text{S:H}_2$	57.35	—	32.90	0.87
Fe(CO)_5	H_2	—	71.70	—	3.99
Fe(CO)_5	$\text{H}_2\text{S:H}_2$	—	60.63	37.6	0.22

1.3. Results and Discussion

1.3.1. Swelling of Coals

Solvent swelling ratios as a function of contact time for four different solvents are given in Tables 4 and 5 for the Texas lignite (PSOC-1444) and the Blind Canyon hvCb (PSOC-1503), respectively. The maximum level of swelling was attained within 6 h; additional solvent-coal contact in excess of 26 h did not produce a significant increase in swelling ratio. The extent of swelling experienced by each coal was slightly different with respect to the individual solvents. For the Texas lignite, swelling increased in order of methanol < THF < pyridine < 10% TBAH; for the Blind Canyon hvCb coal the order was 10% TBAH < methanol < THF < pyridine. The extent of the swelling in the different solvents is rank-dependent. Lignites are more crosslinked than bituminous coals. Therefore, lignites give less swelling and extractability in methanol, THF and pyridine than do bituminous coals. Lignites have higher concentrations of acidic functional groups (phenolic hydroxyl and carboxylic groups) than bituminous coals; therefore, swelling of lignite increases with increasing basicity of

Table 4. Change in solvent swelling ratio (Q) with time for the Big Brown Texas lignite (PSOC-1444)

Methanol		THF		Pyridine		TBAH	
Time (h)	Q	Time (h)	Q	Time (h)	Q	Time (h)	Q
5.0	1.1	6.0	1.2	6.5	1.6	6.0	2.6
11.5	1.1	16.5	1.2	21.5	1.6	14.5	2.6
23.0	1.1	22.0	1.3	42.0	1.6	24.5	2.7
27.5	1.1	28.0	1.3				

Table 5. Change in solvent swelling ratio (Q) with time for the Blind Canyon bituminous coal (PSUC-1503)

Methanol		THF	Pyridine	TBAH (10%)
Time (h)	Q	Q	Q	Q
6.0	1.2	1.9	2.4	1.2
10.0	1.3	1.8	2.3	1.2
20.0	1.3	1.8	2.2	1.2
26.0	1.3	1.8	2.3	1.2

solvents. TBAH is quite basic and has been shown to react strongly with the types of oxygen functionalities in most lower rank coals.²⁰ Our results with the Blind Canyon bituminous coal differ from those of Joseph,¹² who determined for Illinois #6 bituminous coal that the highest swelling was obtained with 15% TBAH (compared with those of THF and methanol). This difference can be explained, at least in part, by the higher oxygen functionality of the Illinois #6 coal than that of the Blind Canyon coal and by the tendency for TBAH to react with these functional groups.²⁰

1.3.2. Comparison of Molybdenum and Iron Catalyst Precursors for Pretreatment

In this section, we discuss results obtained without swelling the coals. Table 6 shows the conversion data for thermal (non-catalytic) reactions and reactions with catalyst-impregnation. Higher total conversion was obtained from Blind Canyon bituminous coal than from Big Brown subbituminous when catalyst was not used (18% vs. 7%). A major contribution to the higher conversion of Blind Canyon is the greatly increased yield of preasphaltenes (11 vs. 3%). This may indicate a greater liberation of mobile phase from the bituminous coal. A greater oil+gas yield is also noted for Blind Canyon (5 vs. 2%). Experiments in $\text{H}_2\text{S}:\text{H}_2$ (5:95) show increased conversions relative to H_2 . This is more noticeable for the subbituminous than for the bituminous coal. This behavior is attributed to the well-known role of H_2S as a liquefaction catalyst. The greater improvement for the subbituminous, relative to the bituminous coal, may indicate H_2S interactions with oxygen functional groups.

The conversions of both coals impregnated with sulfided catalysts are greater than those obtained without catalyst. In the case of Big Brown subbituminous, ATTM improves total conversion slightly (9% vs. 7%). The increased conversion is due to increased asphaltenes and preasphaltenes. MoS_3 also improves conversion slightly. Improvement is via increased preasphaltenes (3% vs. 4%). In the case of Blind Canyon bituminous coal, impregnation with ATTM increased the total conversion from 18% to 25%, mainly as a result of increased preasphaltenes. Oil yield also increased slightly (7% vs. 5%). MoS_3 does even better (27% conversion) by nearly

Table 6. Comparison of Molybdenum and Iron catalysts on the liquefaction of Big Brown subbituminous (DECS-1) and Blind Canyon bituminous coals (DECS-6)

Coal	Catalyst	React. Gas	Conversion% (daf)			
			Total	Preasph	Asphalt	Oil+Gas
DECS-1	None	H ₂	6.6	2.8	2.2	1.6
DECS-1	None	H ₂ S:H ₂	9.0	3.7	2.0	2.3
DECS-1	FeSO ₄	H ₂	6.4	2.4	2.2	1.8
DECS-1	Fe(CO) ₅	H ₂	6.2	2.1	2.3	1.8
DECS-1	Fe(CO) ₅	H ₂ S:H ₂	11.2	4.2	3.5	3.5
DECS-1	ATTM	H ₂	9.0	3.9	3.6	1.5
DECS-1	MoS ₃	H ₂	7.2	3.9	1.7	1.6
DECS-1	Mo(CO) ₆	H ₂	6.7	2.9	2.0	1.8
DESC-1	Mo(CO) ₆	H ₂ S:H ₂	9.1	4.2	2.8	2.2
DECS-6	None	H ₂	17.7	10.7	2.1	4.9
DECS-6	None	H ₂ S:H ₂	18.5	9.7	1.9	6.9
DECS-6	FeSO ₄	H ₂	16.9	9.2	2.6	5.1
DECS-6	Fe(CO) ₅	H ₂	17.3	8.4	1.6	7.3
DECS-6	Fe(CO) ₅	H ₂ S:H ₂	22.9	14.1	2.7	6.1
DECS-6	ATTM	H ₂	25.0	15.1	3.0	6.9
DECS-6	MoS ₃	H ₂	26.9	19.0	3.3	4.6
DECS-6	Mo(CO) ₆	H ₂	16.5	8.1	1.5	6.9
DECS-6	Mo(CO) ₆	H ₂ S:H ₂	26.6	15.7	3.3	7.6

doubling the yield of preasphaltenes (19% vs. 11%). However, the oil yield was not improved with MoS₃. Utz and co-workers have shown that the conversion of Illinois #6 coal with MoS₃ was comparable to that obtained with ATTM.²¹ This entire body of results with ATTM and MoS₃ is in general agreement with previous findings from this laboratory, which have suggested that the principal role of sulfided catalysts in liquefaction is to enhance

conversion via breakdown of the macromolecular structure of the coal, and hence the predominant contribution to enhanced total conversion comes from increased yields of preasphaltenes and asphaltenes.²²

The similarity of results obtained using ATTM and MoS_3 can be explained by the decomposition behavior of ATTM in the reaction system. Thermal analysis of ATTM showed two regions of decomposition (Figure 1). The first decomposition of ATTM occurs around 160°C with loss of 24.5% weight (for the conversion of ATTM to MoS_3 , the calculated weight loss is 26.15%). The second decomposition occurs around 370°C and the total weight loss was 38.8% (from ATTM to MoS_2 the theoretical weight loss is 38.46%). ATTM was reacted at 275°C in hydrogen atmosphere (7MPa cold) without coal in order to determine the fate of ATTM at the preliquefaction conditions used in this work. Elemental analysis of the product shows that it transforms to MoS_{2+x} which contains 3.26% of nitrogen (Table 2). The slightly different activities of these two molybdenum-based catalysts with both coals may be due to a difference in catalyst dispersion for each coal and on the destructive effect of ammonia (released from decomposition of ATTM) on the activity of the molybdenum sulfide catalyst derived from ATTM.

Ferrous sulfate produces no change in conversion or product slate for liquefaction of the Big Brown subbituminous coal. Furthermore, ferrous sulfate is not an active catalyst for liquefaction of the bituminous coal at 275°C . XRD of the product of heating $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ in a microautoclave in the absence of coal showed mono- and tetrahydrated ferrous sulfate phases as the primary products at 275°C . Conversion of ferrous sulfate to an active sulfide phase was achieved only at temperatures in excess of 350°C .

Figure 1. Thermogravimetric and Differential Thermogravimetric Analyses of Ammonium Tetrathiomolybdate

Therefore, ferrous sulfate may only be effective as a high-temperature single-stage catalyst.

The single-particle impregnation studies using a methanol-pretreated or moist surface of the Big Brown subbituminous indicate that a good surface dispersion of ferrous sulfate was achieved (Figures 2 and 3, respectively). Figure 2 illustrates the two crystal types found; one occurred as large prismatic crystals ranging in size from 100 to 300 μm , and the other type occurred as acicular crystals that were distributed as 30 μm size clusters across the coal surface. EDS examination revealed that the larger crystals were ferrous sulfate, whereas the more highly disseminated acicular form was calcium sulfate. At higher magnification (Figure 3), the needle-like clusters of calcium sulfate were found to be associated with a core of ferrous sulfate. When ferrous sulfate in aqueous or methanol solution is applied to a moist lignite surface, ion exchange of iron with organically associated calcium may be promoted. (The calcium content of DECS-1 is 1.2% on a dry basis.) Blind Canyon bituminous coal has much less calcium (0.2%, dry coal basis), but some acicular crystals were observed on the single-particle surfaces among crystals of ferrous sulfate.

Both calcium and iron sulfate particles were observed on surfaces in the particulate samples impregnated with ferrous sulfate in aqueous solution (Figure 4). Different concentrations of iron and calcium sulfates observed between the two coals closely follow those seen with the single-particle samples. However, a much better dispersion of sulfate crystals was observed in the Blind Canyon sample. EDS examination showed that one

Figure 2. Large Crystal of Ferrous Sulfate Surrounded by Smaller Clusters of Acicular Calcium Sulfate as Deposited on a Single Particle of Big Brown (DECS-1) Coal that Was Soaked in Methanol

Figure 3. Acicular Calcium Sulfate Clusters Apparently Growing from a Core of Ferrous Sulfate which Was Seen Following Impregnating a Moist Surface of Big Brown (DECS-1) Coal with Ferrous Sulfate

Figure 4. A Mixture of Ferrous and Calcium Sulfate Crystals Associated with a Blind Canyon (DECS-6) Coal Particle Following Aqueous Impregnation with Ferrous Sulfate

particle in five had an iron peak or had recognizable crystalline material. A similar analysis of the Big Brown subbituminous particulate sample demonstrated that sulfate materials were not as uniformly dispersed, most being found in large deposits not associated with the lignite.

Impregnated iron carbonyl provided no change in conversion of the subbituminous coal in a H_2 atmosphere, but slight increases in asphaltene and oil+gas yields (and thus decreased preasphaltenes) were observed. However, in a $H_2S:H_2$ atmosphere, iron carbonyl provides an increase in conversion (11% vs. 7%), with a doubling of preasphaltenes and increased asphaltenes and oil+gas. For the bituminous coal reacted in H_2 , iron carbonyl does not enhance total conversion, but shifts product slate toward lighter materials at expense of preasphaltenes and asphaltenes. In $H_2S:H_2$, iron carbonyl enhances total conversion (23% vs. 18%), mainly via increased preasphaltenes (14% vs. 11%). Elemental and XRD analyses revealed that $Fe(CO)_5$ transforms to iron oxides with accumulated carbon (FeO and Fe_3O_4) in H_2 and transforms to pyrrhotite in $H_2S:H_2$ (Table 3 and Figure 5). Thus the behavior of the catalyst can be influenced by the choice of atmosphere. In the absence of H_2S , the catalyst is not sulfided, and appears to have no effect at facilitating the breakdown of the coal structure, because the total conversion is essentially unchanged. However, in this system the catalyst does facilitate hydrogenation of the heavier fractions of the subbituminous coal. In $H_2S:H_2$, an increase in conversion (9% vs. 7%) results, primarily from increased asphaltenes and preasphaltenes.

Most prior work on iron oxide formation from catalyst precursors and its subsequent effect on liquefaction has been at temperatures much higher

Figure 5. X-ray Diffractogram of Product Obtained from Reaction of Iron Pentacarbonyl in 5:95 $\text{H}_2\text{S} : \text{H}_2$

than the work we report here. The impregnation of Victorian (Australia) brown coals with ferrous acetate and subsequent reaction initially formed hydrated iron oxides and iron humates.²³ At temperatures $\geq 380^\circ$ in a hydrogen atmosphere, the iron remaining in the liquefaction residue was present as a mixture of magnetite and troilite.²⁴ The magnetite can be converted to iron, which is subsequently transformed to the carbide.²⁵ At reaction temperatures above 400° , it has been shown that improved conversion obtained by addition of iron compounds occurs in the form of increased oil yields.²⁶ In comparison, several other groups have shown that when iron is present in a sulfided form, it helps convert the coal to asphaltenes, but does not facilitate the conversion of asphaltenes to oils.^{24,27,28}

Similar to the findings with iron pentacarbonyl, molybdenum hexacarbonyl in H_2 does not affect conversion of the Blind Canyon bituminous coal, but shifts products to lighter materials. This suggests that molybdenum hexacarbonyl, or its thermal decomposition products, is effective in catalyzing the hydrogenation of preasphaltenes and asphaltenes to oil at 275° in a low-sulfur medium. (No significant beneficial effect was observed with the Big Brown coal.) In $H_2S:H_2$, it enhances conversion, mainly via formation of more preasphaltenes. In the absence of coal, molybdenum hexacarbonyl is largely, but not entirely, unreactive in H_2 , but transforms to a sulfided catalyst in $H_2S:H_2$ (Table 3). Reaction of molybdenum hexacarbonyl in hydrogen at $275^\circ C$ yields a product having the empirical formula (based on elemental analysis) $Mo(CO)_5$. X-ray diffraction of this product shows only molybdenum hexacarbonyl as an identifiable

material, along with some broad peaks indicative of poorly crystalline material. Since molybdenum hexacarbonyl readily sublimes at 110°C, the amount of hexacarbonyl remaining in the reaction product can be estimated easily by a thermogravimetric analysis. For reaction of Mo(CO)_6 in H_2 at 275°C, the product contains 88% unreacted Mo(CO)_6 , as estimated by TGA. (It should be noted that a mixture of 83.3% Mo(CO)_6 and 16.7% Mo would have an elemental composition consistent with an empirical formula Mo(CO)_5 , in good agreement with the TGA result of 88% Mo(CO)_6 .) A small amount of hydrocarbon gases was detected after reaction, suggesting some interaction of CO released by thermal decomposition of the carbonyl with H_2 , in a Fischer-Tropsch-like reaction. The reaction of molybdenum hexacarbonyl in $\text{H}_2\text{S:H}_2$ at 275° gives a product having elemental composition consistent with the empirical formula MoOS_2 , mixed with small amounts of carbon, although we have not unequivocally identified a specific compound of this formula in the product.

Sulfided molybdenum catalysts are well known to be active for hydrogenation. Hydrogen absorption from the gas phase is approximately 18 mg with sulfided molybdenum catalyst at 275°C, while it was almost zero without catalyst for both coals. The gaseous product of the reaction at 275°C is only CO_2 , and varies in the range 0.3–0.6% for the Blind Canyon coal and 1.3–2.5% for the Big Brown subbituminous coal.

1.3.3. The Effect of Preswelling on Non-catalytic Liquefaction

The conversion results of solvent swollen coals without catalyst impregnation are given in Table 7. Treatment with methanol enhanced oil

Table 7. Effect of preswelling treatment on liquefaction of Big Brown subbituminous (DECS-1) and Blind Canyon bituminous (DECS-6) coals at 275°C

Coal	Solvent	Conversion % (daf)			
		Total	Preasph	Asphalt	Oil+Gas
DECS-1	None	6.6	2.8	2.2	1.6
DECS-1	Methanol	8.4	2.2	1.8	4.4
DECS-1	THF	7.4	2.9	0.9	3.6
DECS-1	Pyridine	10.0	1.7	2.0	6.4
DECS-1	TBAH	17.5	5.2	3.9	8.4
DECS-6	None	17.7	10.7	2.1	4.9
DECS-6	Methanol	19.8	12.2	1.6	6.0
DECS-6	THF	22.1	11.1	2.2	9.2
DECS-6	Pyridine	16.0	6.4	1.3	8.2
DECS-6	TBAH	24.0	15.1	3.6	5.3

formation, decreased preasphaltenes and asphaltenes for the Big Brown subbituminous (DECS-1); and enhanced oils and preasphaltenes and decreased asphaltenes for the Blind Canyon coal (DECS-6).

THF is the least effective swelling reagent for the liquefaction of the Big Brown coal, but it provided improved conversion, commensurate with its good swelling ability, for the Blind Canyon coal ($Q = 1.9$). THF pretreatment increased the total conversion of the Blind Canyon coal from 17.7% to 22.1% and oil formation from 4.9% to 9.2%. Its effect on formation of preasphaltenes and asphaltenes was not significant.

Pyridine pretreatment provided greater total conversion and oil formation for the Big Brown subbituminous than those obtained from methanol and THF treatment. However, this treatment diminished the formation of

preasphaltenes from this coal. The pyridine treatment for Blind Canyon coal decreased total conversion from 18% to 16%. A significant reductions in the yield of preasphaltenes, from 11% to 6%, and some decrease in the yield of asphaltenes, from 2% to 1%, were observed. However, the yield of oils increased from 5% to 9%.

TBAH treatment provided the highest conversion for both coals relative to the other solvents, even though a 10% TBAH solution in a 1:1 water:methanol mixture swelled the Blind Canyon coal least. There might be two reasons for the high conversion with TBAH addition to coals. The first is an increased swelling effect that may result as solvent is evaporated. The evaporation of methanol and water from the coal-solvent-TBAH mixture increases the concentration of TBAH in the coal. The TBAH, thus concentrated by evaporation, can increase the level of swelling of the coal, even for Blind Canyon. Second, in a reaction of 40% TBAH in a microautoclave at the same reaction conditions as used for the pretreatment experiments (but without coal), butane and butene were observed in the gaseous products. It can be expected that TBAH likely transformed to amine compounds, such as tributylamine. Therefore, TBAH can be envisioned to act as a "solvent precursor," in that the TBAH remaining in the coal after the swelling procedure can undergo thermal decomposition to compounds that are good solvents for coal. It has been found that amines are very good promoters for coal liquefaction.²⁹⁻³¹ The nitrogen contents of residue, preasphaltenes and asphaltenes were found to be higher for TBAH-swollen coal than those of unswollen coal. This increase is attributed to the incorporation of amines. Therefore, assuming that TBAH transformed to

tributylamine, the amount of tributylamine incorporated in residue, asphaltenes and preasphaltenes can be determined from the difference between the nitrogen contents of these materials and those of the respective products from unswollen coal. The incorporation of amine compound in these products varied between 2-9%. Addition of TBAH provided the highest increase in yields of preasphaltenes, asphaltenes and oil for the Big Brown subbituminous compared to those of coals swollen with other solvents. For the Blind Canyon coal, TBAH addition provided the greatest conversion, yields of preasphaltenes and asphaltenes, but a lower yield of oil relative to those for coals swollen with the other solvents.

For the Big Brown subbituminous, conversion of solvent-pretreated samples without catalyst increased in the order of none ~ THF < methanol < pyridine << TBAH. TBAH and pyridine are the most effective swelling agents, and provide highest conversions of swollen samples. Furthermore, these two solvents also provided the highest oil + gas yields. For the Blind Canyon coal, conversion without catalyst increased in the order of pyridine < none < methanol < THF < TBAH. The behavior of the bituminous coal, with respect to total conversion, is quite different from that of the subbituminous, since in this case pyridine was the most effective swelling solvent, yet pyridine pretreatment actually suppressed total conversion. However, the two best swelling solvents, pyridine and THF, produced the highest oil + gas yields. The extractive ability of a particular solvent is related to the swelling effect of that solvent for a particular coal. A good extractive solvent can disrupt weak bonds in the coal network or in material trapped in the coal structure. Therefore, the molecules released

by this disruption and the weakened structure can be liquefied at less severe conditions.

1.3.4. Combined Effects of Swelling and Catalyst Impregnation

Comparative conversion data for ATTM-impregnated swollen Big Brown subbituminous and Blind Canyon bituminous coal are given in Table 8. A comparison of the results presented in Tables 7 and 8 shows that, for the subbituminous coal swollen with any given solvent, the addition of ATTM improved total conversion relative to that obtained for experiments without catalyst. The increase in total conversion obtained by adding ATTM is approximately the same for all samples, suggesting that the effects of swelling and catalyst impregnation are independent. However, the improvement in conversion obtained by combining ATTM impregnation and swelling is less than that obtained by adding ATTM to unswollen subbituminous coal. For example, impregnation with ATTM increased conversion from 7% to 9% when the subbituminous was not pretreated with solvent, but for the solvent-treated samples the conversions increased only by 1 - 2%. The oil + gas yields are essentially unchanged (relative to the solvent pretreated samples without catalyst) on adding ATTM, with the increase in conversion being obtained via increased yields of preasphaltenes and asphaltenes. Since sulfided molybdenum catalysts appear to act mainly to increase the yields of these two products from unswollen coals, this observation further corroborates the suggestion that the effects of catalyst and swelling solvent are independent. If the effects of swelling and catalyst impregnation are compared with results for

Table 8. Effect of preswelling on liquefaction of Big Brown subbituminous (DECS-1) and Blind Canyon bituminous (DECS-6) coals with ATTM catalyst at 275°C

Coal	Solvent	Conversion % (daf)			
		Total	Preasph	Asphalt	Oil+Gas
DECS-1	None	9.0	3.9	3.6	1.5
DECS-1	Methanol	9.5	2.8	2.2	4.5
DECS-1	THF	9.3	3.1	2.8	3.4
DECS-1	Pyridine	11.8	2.9	2.4	6.5
DECS-1	TBAH	18.7	6.2	4.6	7.9
DECS-6	None	25.0	15.1	3.0	6.9
DECS-6	Methanol	24.7	15.4	2.4	6.9
DECS-6	THF	25.1	12.4	2.4	10.3
DECS-6	Pyridine	26.7	14.6	2.6	9.5
DECS-6	TBAH	23.7	13.5	3.9	6.3

catalyst impregnation without swelling, it can be seen that solvent treatment increases conversion, and that generally the yields of preasphaltenes and asphaltenes are reduced relative to the case without solvent treatment. Hence the solvent swelling facilitates shifting the product slate toward lighter materials. The greatest conversions and formation of all types of products were obtained with TBAH addition. In this case, the TBAH was by far the most effective solvent pretreatment, because the total conversion doubled, relative to the unswollen subbituminous coal, and yields of all products were increased significantly. The order of conversion can be given as none ~ THF ~ methanol < pyridine << TBAH for the Big Brown subbituminous. This is essentially the same as the order obtained without impregnation of ATTM.

For the Blind Canyon bituminous coal, the results are not as consistent as in the case of the subbituminous. The addition of ATTM increased conversions for solvent-treated samples, relative to comparable samples without ATTM, except in the case of TBAH-treated coal. In fact, TBAH addition seemed to decrease the activity of the molybdenum sulfide catalyst, because the conversion of TBAH-treated coal was slightly less than that of the unswollen coal. Again the increased conversion is mainly in the form of enhanced yields of preasphaltenes and asphaltenes. For this coal, the effects of solvent pretreatment on total conversion at 275°C are negligible, but THF, pyridine, and TBAH effect slight changes in the product distribution. THF and pyridine treatments increase oil and gas yields at the expense of preasphaltenes and asphaltenes. TBAH treatment increases asphaltene yield while decreasing preasphaltenes.

One reason for improved conversion and product yield for THF-treated Blind Canyon coal is suggested by Figure 6. This SEM micrograph shows the surface of several coal particles coated with hemispherical bodies following swelling in THF and impregnation with ATTM. These bodies were easily destroyed by a focused electron beam and are carbon-rich. We conclude that this material was part of the THF-soluble fraction that was extracted from the coal during swelling and that was subsequently redeposited on the coal surface when the THF was evaporated before catalyst impregnation. The benefit of this removal and redeposition of THF-solubles could arise in two ways. First, we hypothesize that the separation of the THF-soluble material from the coal during swelling could have created more surface area for catalyst deposition (although we have not measured the

Figure 6. Hemispherical THF-Soluble Deposits on Coal Surface Following Swelling of Blind Canyon (DECS-6) Coal in THF with Subsequent Impregnation with Ammonium Tetrathiomolybdate

Figure 7. Clusters of Plate-Like Crystals of Ammonium Tetrathiomolybdate on the Polished Surface of Big Brown (DECS-6) Coal that Was Pre-Soaked in Methanol

Figure 8. Smaller Ammonium Tetrathiomolybdate Clusters (shown by arrow) Found in a Particulate Sample of Big Brown Lignite (PSOC-1444)

surface areas before and after swelling). Second, conversion of bituminous coals in short contact time, low-temperature liquefaction has been shown to depend on the mobility of the solvent-extractable portion of the coal and its ability to reach catalyst particles on the coal surface.³² The action of THF in bringing some of this mobile material to the coal surface should make it easier for this material to contact the dispersed catalyst. The significant increase in oil + gas yield (Table 7) suggests that by improving access of the THF-soluble fraction to the hydrogenation environment may be beneficial. The improved oil + gas yields and reduced preasphaltene and asphaltene yields shown in Table 8 imply that the increased surface area for catalyst/coal contact resulting from swelling in THF has little influence on conversion of the THF-insoluble fraction of this coal under pretreatment conditions. Improved access of catalyst to the THF-soluble coal fraction does not significantly increase yield relative to the non-catalytic reaction, but may improve overall product quality.

Addition of ATTM in water:methanol solutions was studied for both coals using single particles as well as particulate samples. The distribution of catalyst was the same regardless of the coal or whether the samples were pretreated in methanol. As shown in Figures 7 and 8, when the solvent was evaporated most of the ATTM aggregated in clusters on the coal surface. For the single coal particles (Figure 7), the clusters were generally large. Individual 10 μm platelets of ATTM occurred in some areas of the sample. Coal surfaces in close proximity to the clusters gave no molybdenum or sulfur peaks in EDS, suggesting that ATTM forms a deposit

only on the exterior surface of the coal and does not penetrate deeply into the interior of the particles. In the particulate sample (Figure 8), clusters of ATTM were not found uniformly on all particles, and they were typically much smaller ($<5\ \mu\text{m}$).

Using molybdenum carbonyl in $\text{H}_2\text{S}:\text{H}_2$ atmosphere, in general, little is gained by solvent treatment for the Blind Canyon coal (Table 9). Increased conversion with pyridine is mainly a result of increased asphaltenes. For Big Brown, similar trends are observed as were seen with ATTM and in the non-catalytic reactions. The principal effect of solvent pretreatment is an increase in oil + gas yield. The conversion of this coal increases in the order none $\sim$ THF $<$ methanol $<$ pyridine $<$ TBAH. With iron carbonyl in $\text{H}_2\text{S}:\text{H}_2$ (Table 10), only TBAH addition provided higher conversion for the Big Brown subbituminous, and increases the yields of all products. Other solvent treatments did not enhance total conversion. Pyridine treatment caused an increase of oil+gas yield, and a decrease of preasphaltenes. Solvent treatment provided little improvement in conversion of Blind Canyon coal. TBAH and pyridine pretreatments slightly increased total conversion via an increase of oil + gas yields.

1.4. Conclusions

Without swelling pretreatment, impregnation of both coals with catalyst precursors increased conversion at 275°C . The increased conversion was mainly a result of an increased yield of preasphaltenes. In the absence of catalyst, swelling the Big Brown subbituminous before liquefaction improves conversion, with the increase mainly a result of

Table 9. Effect of preswelling on liquefaction of Big Brown subbituminous (DECS-1) and Blind Canyon bituminous (DECS-6) coals with $\text{Mo}(\text{CO})_6$ at 275°C

Coal	React. Gas	Solvent	Conversion (%)			
			Total	Preasph	Asphalt	Oil+Gas
DECS-1	H_2	None	6.7	2.9	2.0	1.8
DECS-1	$\text{H}_2\text{S}:\text{H}_2$	None	9.1	4.2	2.8	2.2
DECS-1	$\text{H}_2\text{S}:\text{H}_2$	Methanol	10.6	3.2	2.3	5.1
DECS-1	$\text{H}_2\text{S}:\text{H}_2$	THF	9.3	3.3	3.2	2.8
DECS-1	$\text{H}_2\text{S}:\text{H}_2$	Pyridine	13.9	3.1	3.6	7.2
DECS-1	$\text{H}_2\text{S}:\text{H}_2$	TBAH	15.3	4.5	3.5	7.3
DECS-6	H_2	None	16.5	8.1	1.5	6.9
DECS-6	$\text{H}_2\text{S}:\text{H}_2$	None	26.6	15.7	3.3	7.6
DECS-6	$\text{H}_2\text{S}:\text{H}_2$	Methanol	25.7	15.6	3.8	6.3
DECS-6	H_2	THF	15.2	6.8	1.3	7.1
DECS-6	$\text{H}_2\text{S}:\text{H}_2$	THF	27.5	17.4	4.4	5.7
DECS-6	$\text{H}_2\text{S}:\text{H}_2$	Pyridine	28.	15.9	5.7	6.5
DECS-6	$\text{H}_2\text{S}:\text{H}_2$	TBAH	26.4	15.7	6.0	3.8

additional (oil+gas) yield. The relative effectiveness of various solvents for improving conversion is in the same general order as their effectiveness at swelling the coal. Preswelling with methanol or pyridine has little effect on liquefaction of the Blind Canyon coal, but both THF and TBAH provide increased conversion as a result of improved preasphaltene yields. With this coal, the effectiveness of solvents at improving liquefaction is not in the same order as their ability to swell the coal. The combined effect of catalyst addition and swelling is to enhance conversion of the subbituminous, with a doubling of conversion obtained by impregnation with catalyst and swelling by TBAH. The yields of all

Table 10. Effect of preswelling on liquefaction of Big Brown subbituminous (DECS-1) and Blind Canyon bituminous (DECS-6) coals with $\text{Fe}(\text{CO})_5$ in $\text{H}_2\text{S}:\text{H}_2$ (5:95) at 275°C

Coal	Solvent	Conversion% (daf)			
		Total	Preasph	Asphalt	Oil+Gas
DECS-1	None	11.2	4.2	3.5	3.5
DECS-1	Methanol	9.7	2.5	3.6	3.6
DECS-1	THF	10.7	3.5	2.3	4.9
DECS-1	Pyridine	11.0	1.8	3.0	6.2
DECS-1	TBAH	23.6	7.5	10.0	6.1
DECS-6	None	22.9	14.1	2.7	6.1
DECS-6	Methanol	19.8	9.8	2.3	7.7
DECS-6	THF	20.6	10.2	3.0	7.4
DECS-6	Pyridine	23.6	11.7	3.1	8.8
DECS-6	TBAH	25.6	11.7	3.7	10.2

products are enhanced by this pretreatment. In contrast, little improvement in total conversion of the Blind Canyon coal is obtained by combining catalyst impregnation and solvent swelling, but changes in the relative proportions of the products can be obtained.

Investigation of catalyst impregnation of solvent-swollen or moist coals with SEM demonstrates that ferrous sulfate and ATTM form only surface dispersions. Pretreatment in methanol or THF appears to have little influence on impregnation. Impregnation with ATTM before and after solvent swelling results in a surface dispersion. Aggregates of small crystals were observed on the surface of single particles and on particulate samples. Molybdenum and sulfur peaks were not detected in areas where these crystals were absent.

The results with $\text{Fe}(\text{CO})_5$ in the different gas atmospheres are noteworthy because they suggest the possibility of tailoring the catalyst action to the characteristics of the coal and the kind of transformations desired. We have shown elsewhere that sulfided catalysts generally seem to intervene in the initial breakdown of the coal, producing preasphaltenes and asphaltenes.²² For coals which do not have a high inherent reactivity, a catalyst facilitating breakdown of the structure may be very useful. On the other hand, some coals appear to undergo a facile thermal depolymerization even in the absence of catalyst, and in such cases a catalyst that acts mainly to help hydrogenate heavier products to oils might be preferable. We have demonstrated with impregnated $\text{Fe}(\text{CO})_5$ that the choice of atmosphere, H_2 vs. $\text{H}_2\text{S}:\text{H}_2$, provides the opportunity of generating an active catalyst that acts either for coal breakdown or for shifting the product slate to lighter materials. It is interesting to speculate that one could, for example, use a $\text{H}_2\text{S}:\text{H}_2$ atmosphere to provide a sulfided, dissolution catalyst for the first stage, re-impregnate with $\text{Fe}(\text{CO})_5$ between stages, and use a H_2 atmosphere in the second stage to enhance hydrogenation of the preasphaltenes and asphaltenes.

An added benefit of solvent swelling could be the formation of good solvent inside the coal, as in the case of the thermal decomposition of TBAH to tributylamine. Previous work in this laboratory has shown that the transport of the mobile phase to catalyst particles on the surface of the coal is an important factor in short-contact time liquefaction of bituminous coals.³² The use of a good swelling agent as a "solvent precursor," with subsequent in situ generation of a good extractive solvent

could increase the amount of mobile phase moving out of the coal and reduce its viscosity. In addition, we have also shown that combining an excellent hydrogen donor (tetrahydro-quinoline) into the same molecular species as a catalyst precursor facilitates hydrogenation by keeping the donor in, or near, the catalyst.³³ Hence the prospect exists for future developments of combined "solvent-and-catalyst precursors."

It is important to recognize that the first-stage liquefaction reactions of coals may produce changes in coal structure or behavior that significantly enhance conversion in the second, high-temperature stage, but which are not necessarily evident in the macroscopic characteristics (e.g., formation of soluble materials) of the products of the first stage. That is, a particular coal-catalyst-solvent combination may provide small conversions or yields of soluble products at the end of the first stage, yet may have experienced subtle changes of structure which then facilitate significant conversion in the second stage. Hence the ultimate assessment of the utility of catalyst impregnation, solvent swelling, or both in improving liquefaction behavior in temperature-staged processes is to determine conversions and product yields at the end of the second stage. Such work is in progress in our laboratory and the results will be reported in due course.

1.5. Acknowledgements

The authors are pleased to acknowledge useful discussions with Dr. Joseph T. Joseph of the Amoco Corporation.

References

1. Weller, S. W. and Pelipetz, M. G. *Ind. Eng. Chem.* , 1951, 43, 1243.
2. Hawk, C.O. and Hiteshue, R.W. *U.S. Bur. Mines Bulletin*, 1965, No. 622.
3. Bodily, D.M., Shibaoka, M. and Yoshida, R. *Proc. 1981 Internat. Conf. Coal Sci.*, 350.
4. Terrer, M.T. and Derbyshire, F.J. *U.S. Dept. of Energy Report*, 1986, No. DOE-OC-60811-F1.
5. Stansberry, P.G. and Derbyshire, F.J. *U.S. Dept. of Energy Report*, 1988, No. DOE-PC-60811-F3.
6. Garcia, A.B. and Schobert, H.H. *Fuel*, 1989, 68, 1613.
7. Bodily, D.M. and Wann, J.P. *Amer. Chem. Soc. Div. Fuel Chem. Prepr.* 1986, 31(4), 119.
8. Suzuki, T., Yamada, O., Then, J.H. and Ando, T. *Proc. 1985 Internat. Conf. Coal Sci.*, 205.
9. Watanabe, Y., Yamada, O., Fujita, K., Takegami, Y. and Suzuki, T. *Fuel*, 1984, 63, 752.
10. Tierny, J.W. and Wender, I. *Proc. DOE Direct Liquefaction Contractors' Review*, 1988, 39.
11. Rincon, J.M. and Cruz, S. *Fuel*, 1988, 67, 1162.
12. Joseph, J.T. *Fuel*, 1991 70, 139.
13. Baldwin, R.M., Kennar, D.R., Nguanprasert, O. and Miller, R.L. *Fuel*, 1991, 70, 429.
14. Comolli, A.G., MacArthur, J.B. and McLean, J.B. *Proc. EPRI Contractors' Conf. on Clean Liquid and Solid Fuels*, 1985, 2-1.
15. Derbyshire, F.J., Davis, A., Lin, R., Stansberry, P.G. and Terrer, M.T. *Fuel Proc. Technol.*, 1986, 12, 127.
16. Solomon, P.R., Serio, M.A., Deshpande, G.V., Kroo, E., Schobert, H.H. and Burgess, C.E. in "Coal Science II" (Eds. H.H. Schobert, K.D. Bartle and L.J. Lynch), American Chemical Society, Washington, 1991, Chapter 15.
17. Derbyshire, F.J., Davis, A., Epstein, M., and Stansberry, P. *Fuel*, 1986, 65, 1233.

18. Davis, A., Derbyshire, F.J. and Schobert, H.H. U.S. Dept. of Energy Report, 1988, No. DOE-DE-FG22-86PC90910-3.
19. Naumann, A.W. United States Patent, 1981, No. 4243554.
20. Liotta, R., Rose, K. and Hippo, E. J. Organic Chemistry, 1981, 46, 277.
21. Utz, B.R., Cugini, A.V. and Frommell, E.A. Amer. Chem. Soc. Div. Fuel Chem. Prepr. 1989, 34(4), 1423.
22. Burgess, C.E., Artok, L. and Schobert, H.H. Amer. Chem. Soc. Div. Fuel Chem. Prepr. 1991, 36(2), 462.
23. Cook, P.S., and Cashion, J.D. Fuel 1987, 66, 661.
24. Cook, P.S., Lim, S.C., Hang, G.S., Jackson, W.R., and Cassidy, P.J. Fuel 1988, 67, 942.
25. Cook, P.S., and Cashion, J.D. Fuel 1987, 66, 669.
26. Cassidy, P.J., Hertan, P.A., Jackson, W.R., Larkins, F.P., and Rash, D. Fuel 1982, 61, 939.
27. Larkins, F.P., Jackson, W.R., Rash, D., Hertan, P.A., Cassidy, P.J., Marshall, M., and I.D. Watkins. in "The Chemistry of Low-Rank Coals" (Ed. H.H. Schobert), American Chemical Society, Washington, 1984, Chapter 18.
28. Pradhan, V.R., Herrick, D.E., Tierney, J.W., and Wender, I. Energy Fuels 1991, 5, 712.
29. Kazimi, F., Chen, W.Y., Chen, J.K., Whitney, R.R. and Zimny, B. Amer. Chem. Soc. Div. Fuel Chem. Prepr. 1985, 30(4), 402.
30. Tagaya, H., Sugai, J., Onuki, M. and Chiba, K., Energy and Fuels, 1987, 1, 397.
31. Miller, R. L., Baldwin, R. M. and Kennar, D. R. Amer. Chem. Soc. Div. Fuel Chem. Prepr. , 1990, 35(1), 9.
32. Chamberlin, P.L. and Schobert, H.H. Fuel Proc. Technol., 1991, 28, 67.
33. Burgess, C.E. and Schobert, H.H. Fuel, 1991, 70, 372.

END

**DATE
FILMED**

7 / 8 / 92