Comparative Study of the Reactions of Metal Oxides
with H_2S and SO_2

Technical Progress Report
for the Period October-December 1991

Received by OSI
MAR 1 8 1992

Prepared by:

Stratis V. Sotirchos

December 1991

Work Performed under Grant No.: DE-FG22-90PC90301

Performed for:

U.S. Dept. of Energy
University Coal Research Program
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

Performed at:

University of Rochester
Dept. of Chemical Engineering
Rochester, NY 14627

MASTER

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EXECUTIVE SUMMARY

This quarterly report presents technical progress made during the fourth calendar quarter of 1991 on a comparative investigation of the reactions of porous metal oxides with sulfur dioxide and hydrogen sulfide. The report is divided into two parts. In the first part, a statement of the work proposed to be carried out under this project is given and the various tasks associated with the project are identified and outlined. In the second part, the work carried out during the above mentioned period is described.

The primary objective of this project is the investigation of the effects of pore structure on the capacity of porous metal oxides for removal of gaseous pollutants from flue gases of power plants (SO_2) and hot coal gas (primarily H_2S). Specifically, we intend to appropriately exploit the differences of the sulfidation and sulfation reactions (for instance, different molar volumes of solid products) to elucidate the dependence of the sorptive capacity of a porous sorbent on its physical microstructure. The following tasks have been identified in the proposed project:

1. Literature survey and identification of solids to be used in experimental studies.
2. Experimental study of the reaction of the chosen solids with SO_2 and/or H_2S .
3. Experimental study of the evolution of the structure of the solids during reaction with SO_2 and/or H_2S using pore structure analysis and effective diffusivity measurements.
4. Model testing and validation using the obtained experimental data.

During the fourth quarter of the 1991 calendar year, work was primarily done on Tasks 2 and 4. A brief description of the work done is given below.

We carried out a detailed characterization of the pore structure of the three limestone solids that served as precursors in our $\text{CaO-H}_2\text{S}$ experiments. This was done because we decided our future experimental efforts to focus on the comparative study of the direct reaction of calcium carbonate solids with H_2S and SO_2 , that is in the presence of enough CO_2 to prevent decomposition of CaCO_3 to CaO . In the case of SO_2 , this is the situation encountered in PFBC (pressurized fluidized bed combustion) units, while for H_2S , it may occur in a desulfurization reactor operating at high pressures and involving coal gas containing a significant amount of CO_2 . Mercury porosimetry and gas adsorption measurements were used for the characterization of the solids. We completed a manuscript on our results for the reaction of limestone-derived calcines with H_2S and the comparison of these results with sulfation data for the same solids from past studies of my research group. Finally, we presented two papers at the 1991 Annual AIChE Meeting (Los Angeles, November 1991) entitled "Transient vs. Steady-State Measurement of Effective Diffusivities in Porous Media Using the Diffusion-Cell Method" and "Experimental Validation of a Model for Fixed-Bed Desulfurization Reactors" (with E. Efthimiadis).

JAN 06 1992

TABLE OF CONTENTS

EXECUTIVE SUMMARY	11
STATEMENT OF WORK	1
1. Project Objectives	1
2. Introduction	1
3. Outline of Project Tasks	3
4. Schedule and Milestones	4
TECHNICAL PROGRESS IN THE PERIOD 10/91-12/91 BY TASK	5
LITERATURE CITED	6
APPENDIX: Efthimiadis, E.A., and Sotirchos, S.V., "Sulfidation of Limestone-Derived Calcines"	

LIST OF FIGURES

Fig. 1. Schedule of project tasks.	4
Fig. 2. Cumulative pore volume curves obtained from N ₂ adsorption-desorption data.	8

LIST OF TABLES

Table 1. Surface areas and porosities of limestone precursors.	8
--	---

STATEMENT OF WORK

1. PROJECT OBJECTIVES

The primary objective of this project is the investigation of the effects of pore structure on the capacity of porous metal oxides for removal of gaseous pollutants from flue gases of power plants (SO_2) and hot coal gas (primarily H_2S). Porous calcines obtained from natural precursors (limestones and dolomites) and sorbents based on oxides of zinc, iron, and/or copper will be used as model systems in our experimental studies, which will include reactivity evolution studies and pore structure characterization using a variety of methods. Our work will focus on oxides that can react (sufficiently fast) both with SO_2 and H_2S . We intend to appropriately exploit the differences of the sulfidation and sulfation reactions (for instance, different molar volumes of solid products) to elucidate the dependence of the sorptive capacity of a porous sorbent on its physical microstructure.

2. INTRODUCTION

The reactions of metal oxides with sulfur-containing compounds, such as SO_2 and H_2S , find extensive use in controlling emissions of gaseous pollutants from coal utilization systems. Limestone and dolomite, for instance, are used in the control of emissions of sulfur dioxide from coal-fired power plants. In the high temperature environment of a combustor, the limestone or dolomite particles undergo calcination, and the calcined product (CaO or MgO) reacts with the sulfur dioxide produced during coal combustion forming, mainly, calcium or magnesium sulfate. Calcium oxide and other metal oxide sorbents (iron oxide, zinc oxide, zinc ferrite, zinc titanate, etc.), on the other hand, are used to remove sulfur-containing compounds (predominantly H_2S) from hot coal gas.

The reaction of metal oxides with SO_2 and H_2S are typical examples of noncatalytic gas solid reactions with solid product formation and pore closure behavior. Such gas-solid reactions with solid product are encountered in a number of chemical process industries with applications ranging from ceramic material manufacture to gas scrubbing for pollution control. The calcination and sulfation reactions of limestone and dolomite have been the subject of extensive experimental investigation, but unambiguous experimental evidence that leads to a clear understanding of the effects of pore size distribution of calcined stones on their capacity for SO_2 removal is still lacking. Most investigators tend to focus on the global kinetics of the sulfation or sulfidation reactions while paying little attention to the pore structure of the calcined solid. As a result, the identification of sorbents exhibiting optimal reactivities and capacities for pollutant removal still remains an essentially haphazard, hit-or-miss operation. A review of the experimental evidence of the literature reveals an anomalous dependence of the reactivity and SO_2 uptake of calcined limestones on the initial values of average properties of their pore structure, such as porosity and surface area, indicating strong effects of the pore size distribution on the overall reactivity of the calcined solids (Borgwardt and Harvey, 1972; Wen and Ishida, 1973; Hartman and Coughlin, 1974, 1976; Ulerich et al., 1977; Vogel et al., 1977; Hasler et al., 1984; Simons and Garman, 1986; Yu, 1987; Gullett and Bruce, 1987).

Analogous observations apply to the reaction of metal oxides (calcium oxide, zinc oxide, zinc ferrite, zinc titanate, etc.) with H_2S . A good deal of experimental effort has been put in the area of hot gas desulfurization into the investigation the reactivity and capacity of various metal/metal oxide

sorbents for sulfur compound removal from coal gas (e.g., see studies by Gibson and Harrison (1980), Tamhankar et al., (1981 and 1985), Ranade and Harrison (1981), Jalan (1983), Anderson et al. (1984), Sick and Schwerdtfeger (1987), and Sa et al. (1989)). However, limited work has been done on the characterization of these sorbents in terms of their pore size distribution and resistance for intraparticle diffusion. Simplistic models of structure evolution are usually employed for data treatment and interpretation, while few studies have looked into the variation of the properties of the pore structure, such as the internal surface area (Caillet and Harrison, 1982; Sa et al., 1989), with the progress of the reaction.

A systematic investigation of the dependence of the transient behavior of large limestone particles reacting with SO_2 in the presence of oxygen on pore structure and particle size related factors has been carried out by my research group (Zarkanitis and Sotirchos, 1989; Yu, 1987). Our results have shown strong dependence of the transient behavior of reacting particles of calcined limestone and, consequently, of their sorptive capacity for SO_2 removal on their initial pore size distribution, but this dependence seems to follow an anomalous pattern when the sulfation capacities of calcines obtained from different precursors (stones) are compared. Specifically, calcines of similar composition and pore structure properties have been found to exhibit considerably different capacities for removal of SO_2 from flue gases. Comparison of the experimental data with the predictions of a generalized pore model for gas-solid reactions with solid product (Yu and Sotirchos, 1987) showed that these differences could be due to the formation of inaccessible pore space in the course of the reaction, which takes place when the small feeder pores of finite clusters of large pores or large cavities, in aperture-cavity pore structures, are filled with solid product.

Similar conclusions have been reached by analyzing reactivity data for zinc oxide sulfidation obtained in our laboratory (Efthimiadis and Sotirchos, 1989). However, an important difference exists between the reaction of metal oxides with H_2S and their reaction with SO_2 . The sulfide produced during reaction with H_2S occupies less space than the solid product produced during sulfation (sulfate (mainly) or sulfite), and as a result, complete pore closure in the case of sulfidation can happen only for low initial porosities. In the case of CaO , for instance, the initial porosity should be lower than 38% for pore closure to occur during sulfidation, while during sulfation pore closure is possible even for initial porosities as high as 65%. Thus, porous CaO with 50% initial porosity can reach complete conversion during sulfidation but only about 50% conversion during sulfation. These differences suggest that a comparative study of the reactions of porous metal oxides with SO_2 and H_2S can lead to a better assessment of the effects of pore structure on sorptive capacity than studies of the effects of the parameters of a single reaction only. Nevertheless, our survey of the literature on sulfation and sulfidation reactions has not uncovered any comparative study of the two processes.

Based on the above observations, a research program has been proposed for the comparative investigation of the reactions of metal oxides with SO_2 and H_2S . Particular emphasis will be placed on the connectivity of the pore space of the solids and the formation of inaccessible pore space in the course of the sulfation or sulfidation process. In order to be able to assess the effects of the formation of inaccessible pore space, a detailed characterization of the pore structure of fresh and partially reacted samples will be carried out using gas adsorption, mercury porosimetry, and photomicrographic methods. A detailed investigation of the effects of the various parameters on the sorptive capacity of the solids will be carried out (e.g., concentration of SO_2 or H_2S , composition of reactant mixture, particle size, and reaction temperature).

The following tasks have been identified in the proposed project:

1. Literature survey and identification of solids to be used in experimental studies.
2. Experimental study of the reaction of the chosen solids with SO_2 and/or H_2S .
3. Experimental study of the evolution of the structure of the solids during reaction with SO_2 and/or H_2S using pore structure analysis and effective diffusivity measurements.
4. Model testing and validation using the obtained experimental data.

These tasks are outlined in the following section.

3. OUTLINE OF PROJECT TASKS

Task 1. Literature survey and identification of solids to be used in experimental studies

Calcines from natural precursors (limestones and dolomites) and commercially available desulfurization sorbents (e.g, zinc oxide) of qualitatively (or quantitatively) different pore size distributions of will be used in our experiments. Our initial experiments will be carried out using solids whose reaction with SO_2 (calcines) or H_2S (zinc oxide-based) has been studied in detail in past studies by our group. Literature survey and consultation with scientists from PETC and METC will help us identify other sorbents to be used in the experiments.

Task 2. Experimental study of the reaction of the chosen solids with SO_2 and/or H_2S

Reactivity Experiments will be carried out for a wide range of particle size -- in order to isolate the effects of the formation of inaccessible pore space from those of other factors -- and in a rather wide concentration and temperature range. Reactivity vs. time or conversion vs. time studies will be conducted using thermogravimetry and fixed-bed and fluidized-bed reactors.

Task 3. Experimental study of the evolution of the structure of the solids during reaction with SO_2 and/or H_2S using pore structure analysis and effective diffusivity measurements

The pore structure of partially reacted samples collected at selected time instants or conversion levels will be analyzed by gas adsorption, using a Quantachrome Autosorb 1 system, and by mercury porosimetry, using a Micromeritics Autopore 9220 II unit. The structure of the porous solids will also be analyzed by photomicrographic methods, such as optical and scanning electron microscopy. Adsorption isotherms may also be determined using flow-type and thermogravimetric apparatuses available in our laboratory. For better characterization of the pore structure of the solid samples we will also carry out intraparticle diffusivity measurements by the peak-broadening (chromatographic) method, using a system developed for this purpose in our laboratory. The fluidized-bed reactor will be used to prepare the relatively large amounts of partially reacted solid that are needed for diffusivity measurements by the peak-broadening method.

Task 4. Model testing and validation using the obtained experimental data

A class of detailed models for transport, reaction, and structure evolution

in chemically reacting porous media, developed by our research group, will be used for the analysis of the obtained reactivity and structure evolution data. Conversely, the experimental data from the fixed-bed and fluidized-bed reactors will be used to test and validate design models for these types of desulfurization reactors. analyze the experimental data obtained from our reactivity studies.

4. SCHEDULE AND MILESTONES

A tentative schedule for execution of the project tasks is shown in Fig. 1, and a list of project milestones for each task follows.

Fig. 1. Schedule of Project Tasks.

Task 1. Milestones

1.1. Literature survey of previous work and selection of first batch of sorbents to be used in experimental studies completed, 1/91.

1.2. Final decision on other sorbents to be used in experiments made, 8/92.

Task 2. Milestones

2.1. Reactivity evolution studies for the first batch of sorbents completed, 4/92.

2.1. Reactivity evolution studies for the second batch of sorbents completed, 3/93.

Task 3. Milestones

3.1. Pore structure characterization of the first batch of sorbents completed, 4/92.

3.2. Pore structure characterization of the second batch of sorbents completed, 3/93.

3.3. Diffusivity measurements for the first batch of sorbents completed, 6/92.

3.4. Diffusivity measurements for the second batch of sorbents completed, 5/93.

Task 4. Milestones

4.1. Testing of single particle models completed, 3/93.

4.2. Validation of reactor models completed, 8/93.

TECHNICAL PROGRESS IN THE PERIOD 9/91-12/91 BY TASK

Task 2

Our future reactivity evolution experiments will concentrate on the comparative study of the direct reaction of calcium carbonate solids with H_2S and SO_2 , that is in the presence of enough CO_2 to prevent decomposition of CaCO_3 to CaO . In the case of SO_2 , this is the situation encountered in PFBC (pressurized fluidized bed combustion) units, while for H_2S , it may occur in a desulfurization reactor operating at high pressures and involving coal gas containing a significant amount of CO_2 .

A detailed characterization of the pore structure of the three limestone solids that served as precursors in our $\text{CaO-H}_2\text{S}$ experiments was thus carried out. Mercury penetration experiments using a Micromeritics 9220 II mercury porosimeter showed that the stones were nearly nonporous in their natural state as only minute quantities (typically, 0.01-0.02 cc/g) of mercury appeared to penetrate the void space of the samples. Since mercury intrusion mainly occurred at high pressures, where sample and mercury compressibility may introduce significant errors in the interpreted data for small intrusion volumes, it was decided to base the analysis of the pore structure of the structure of unreacted and partially reacted solids on gas adsorption data instead. Gas adsorption isotherms (N_2 at 77 K) were measured using a volumetric adsorption instrument (Autosorb-1 by Quantachrome). The relatively large quantities of partially reacted samples needed for the porosimetry and adsorption experiments were prepared in a fixed bed reactor under differential operation at the same conditions used in the TGA experiments. The differential operation of the reactor was verified using a gas chromatograph (Varian 3300) equipped with a flame photometric detector to analyze the effluent stream.

Fig. 2 presents cumulative pore volume vs. pore radius results for the three limestones obtained through gas N_2 adsorption at 77 K. The porosities for pores of radius smaller than 1000 Å and the surface areas determined from BET analysis of the results of Fig. 2 are shown in Table 1. Greer limestone is seen to have the highest natural porosity followed by Georgia marble and Iceland spar. The surface areas show the same trend as the porosities, with Greer limestone having about three times larger surface area than Georgia marble and four times than Iceland spar. Interestingly enough, the sulfation and sulfidation rates of calcines derived from these solids were found (see our report on Task 4) to increase in the same order as the porosities and surface areas of the precursors, while, on the contrary, the average grain size of the precursors, as revealed by the petrographic analysis of the solids, decreases. This observation indicates that the petrographic texture of a limestone must play an important role in determining its performance as a sorbent for SO_2 or

H₂S removal under both calcining and noncalcining conditions.

Task 4

A detailed account of our results on the comparative study of the reaction of calcines derived from the above solids with H₂S and SO₂ is given in a manuscript attached as an appendix to this report.

LITERATURE CITED

- Anderson, G.L., Berry, F.O., and M.N. Gross, "Development of a Hot Gas Cleanup System for Integrated Coal Gasification/Molten Carbonate Fuel Cell Power Plants," Topical Report, DOE/MC/19403-1544, 1984.
- Borgwardt, R.H. and R.D. Harvey, Environ. Sci. Technol., 6, 350 (1972).
- Caillet, D.A. and D.P. Harrison, Chem. Eng. Sci., 37, 625 (1982).
- Efthimiadis, E.A. and S.V. Sotirchos, "Reactivity Evolution during Sulfidation of Porous Zinc Oxide," AIChE Annual Meeting, San Francisco, CA, 1989.
- Gibson, J.B. and D.P. Harrison, Ind. Eng. Chem. Process Des. Dev., 19, 231 (1980).
- Gullett, B.K. and K.R. Bruce, AIChE J., 33, 1719 (1987).
- Hartman, M. and R.W. Coughlin, Ind. Eng. Chem., Process Des. Dev., 13, 248 (1974).
- Hartman, M. and R.W. Coughlin, AIChE J., 22, 490 (1976).
- Hasler J.R. et al., "Testing of limestone samples from the TVA region as sulfur dioxide sorbents in atmospheric fluidized bed combustors," Technical Report, Institute for Mining and Mineral Research, Univ. of Kentucky, 1984.
- Jalan, V., "Studies Involving High Temperature Desulfurization/Regeneration Reactions of Metal Oxides for Fuel Cell Development," Final Report, DOE/MC/16021-1486, 1983.
- Ranade, P.V. and D.P. Harrison, Chem. Eng. Sci., 36, 1079 (1981).
- Sa, L.N., G.D. Focht, P.V. Ranade, and D.P. Harrison, Chem. Eng. Sci., 44, 215 (1989).
- Sick, G. and K. Schwerdtfeger, Met. Transactions B, 18, 603 (1987).
- Simons, G.A. and A.R. Garman, AIChE J., 32, 1491 (1986).
- Tamhankar, S.S., Garimella, S., and C.Y. Wen, Chem. Eng. Sci., 40, 1019 (1985).
- Tamhankar, S.S., Hasatani, M., and C.Y. Wen, Chem. Eng. Sci., 36, 1181 (1981).
- Ulerich, N.H., E.P. O'Neill, and D.L. Keairns, "The Influence of Limestone

Calcination on the Utilization of the Sulfur-Sorbent in Atmospheric Pressure Fluid-Bed Combustors," EPRI ER-426, Final Report, 1977.

Vogel, G.J. et al., Quarterly Report (January-March 1977), prepared for DOE, Argonne National Laboratory, 1977.

Wen, C. Y. and M. Ishida, Environ. Sci. Technol., 7, 703(1973).

Yu, H.C., Ph.D Thesis, University of Rochester, 1987.

Yu, H.C. and S. V. Sotirchos, AIChE J., 33, 382 (1987).

Zarkanitis, S. and S.V. Sotirchos, AIChE J., 35, 821 (1989).

Fig. 2. Cumulative pore volume curves obtained from N_2 adsorption-desorption data.

TABLE 1. Surface Areas and Porosities of Georgia Marble, Greer Limestone, and Iceland Spar Precursors.

Limestone	Particle size (μm)	Surface Area (m^2/g)	Porosity ($< 1000 \text{ \AA}$ in radius pores)
Greer Limestone	53-62	0.91	0.015
Georgia Marble	53-62	0.31	0.007
Iceland Spar	53-62	0.23	0.004

(print removed)

END

DATE
FILMED

4 / 30 / 92