365
7-2-86

NE-F--9-4T-Rev.2/84

DE93 011216

OAK RIDGE NATIONAL LABORATORY

OPERATED BY MARTIN MARIETTA ENERGY SYSTEMS, INC

NUCLEAR STANDARDS TRANSMITTAL

ATT.	DISTRIBUTION	RETURN COMMENTS TO ORNL Standards Coordinator	DATE June 30, 1986	
List 01 05		NO LATER THAN	TYPE SUBMISSION	
		COGNIZANT ENGINEER	☐ 1. TENTATIVE ☐ 2. DRAFT ☐ 3. AMENDMENT ☒ 4. REVISIONS ☐ 5.	
		J. J. Blass		
		PHONE		
		Com. 615-574-0721		
FTS 624-0721	TYPE ACTION			
			☒ A. TRIAL USE ☐ B. INFORMATION ☐ C. COMMENTS ☐ D.	
		NUMBER	DESCRIPTION	ACTION
		NE F 9-4T	Requirements for Design of Class 1 Elevated Temperature Nuclear System Components (Supplement to ASME Code Case N-47)	A

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

EB

Perk Cooper
 William L. Cooper, Jr., Manager
 Performance Assurance Project Office

FOREWORD

This standard supersedes the February 1984 issue of NE F 9-4T. In addition to numerous editorial changes throughout the document, the following revisions have been made:

Subparagraph N-3241(c) has been added providing a procedure to determine whether further consideration of nonductile fracture is necessary.

Paragraph N-3253 has been added requiring that a creep fatigue interaction test be performed for each lot of material when service conditions exceed specified limits.

Subparagraph A-3611(d) of the February 1984 issue, on special requirements for piping components, has been removed since these are provided in paragraph T-1326 of the latest edition of Code Case N-47 (N-47-22, April 1984).

Table and Figure NT-1430-1D have been added providing design fatigue curves for elastic analysis of 2-1/4 Cr-1 Mo Steel.

Paragraphs NT-1440 to NT-1442 have been added providing alternate limits for thermal striping of type 316 stainless steel.

June 1986

i

i

REQUIREMENTS FOR DESIGN OF CLASS 1 ELEVATED TEMPERATURE NUCLEAR SYSTEM
COMPONENTS (SUPPLEMENT TO ASME CODE CASE N-47)

TABLE OF CONTENTS

	<u>Page</u>
1. INTRODUCTION	1
1.1 Scope	1
1.2 Organization of Standard	1
1.3 Revisions	1
1.4 Conflicts	2
1.5 Applicable Documents	2
2. SUPPLEMENTS TO CODE CASE N-47	2
-1000 INTRODUCTION	2
N-1200 Structural Evaluation Program	2
-3000 DESIGN	3
-3100 General Requirements for Design	3
-3200 Design by Analysis	3
-3300 Vessel Design	6
APPENDIX I-14, TABLES I-14.0	7
APPENDIX T RULES FOR STRAIN, DEFORMATION, AND FATIGUE LIMITS AT ELEVATED TEMPERATURES	7

REQUIREMENTS FOR DESIGN OF CLASS 1 ELEVATED TEMPERATURE NUCLEAR SYSTEM COMPONENTS (SUPPLEMENT TO ASME CODE CASE N-47)

1. INTRODUCTION

1.1 Scope. This standard provides rules for the design of Class 1 nuclear components for use at elevated temperatures. It constitutes a complete set of requirements only when used in conjunction with Section III of the ASME Boiler and Pressure Vessel Code (ASME Code) and addenda, and ASME Code Case N-47. Unmodified portions of Code Case N-47 are not repeated in this standard but are considered requirements of this standard.

1.1.1 Applicability. The applicability of this standard is consistent with that of Section III of the ASME Code as modified by Code Case N-47.

1.1.2 Definitions. The definitions of terms used in NE F 9-4T are consistent with those employed by Section III of the ASME Code as modified by Code Case N-47.

1.2 Organization of Standard. This standard contains requirements that supplement those of Code Case N-47. The organization of this standard corresponds to the section, article, paragraph, figure, and equation designations of the Code Case.

Requirements that supplement or replace an existing Code Case article, paragraph, or portion thereof are designated in this standard by the corresponding Code Case number prefixed with an "A." For example, the addition to subparagraph -3214.3 is designated "A-3214.3."

New requirements are designated by the next available number in the Code Case sequence for similar requirements, prefixed with an "N." For example, the new subarticle of this standard that is to be added to article -1000 is designated as "N-1200."

Standard NE F 9-5T is a nonmandatory standard that supplements this standard and provides the manufacturer with general guidelines and procedures to satisfy the requirements of this standard. It addresses guidelines for the stress analysis aspects of design and supplies procedures for consideration and use by the manufacturer.

1.3 Revisions. Revisions of this standard, or the reference documents in 1.5, effective later than those specified in the Design Specifications may be used only by mutual consent of the Owner and the Manufacturer.

1.4 Conflicts. The requirements of this standard shall not be construed to relieve any party of responsibility for meeting the requirements of the ASME Code. Where this standard appears to conflict with the requirements of a referenced document, this shall be immediately brought to the attention of the owner for resolution.

1.5 Applicable Documents. The following documents are a part of this standard to the extent specified herein.

1.5.1 Nuclear Energy Standards.

NE F 9-5T Guidelines and Procedures for Design of Class 1 Elevated Temperature Nuclear System Components

1.5.2 American Society of Mechanical Engineers (ASME) Boiler and Pressure Vessel Code.

Section III Rules for the Construction of Nuclear Power Plant Components

Case N-47-22 Class 1 Components in Elevated Temperature Service, Section III, Division 1

1.5.3 Other Documents.

TID-26666 Nuclear Systems Materials Handbook

1.5.4 Applicable Version of ASME Code. This standard, in referring to sections of the ASME Code, refers specifically to the 1983 Edition, including all applicable addenda. The term "Code Case N-47" refers specifically to the revision identified in 1.5.2.

2. SUPPLEMENTS TO CODE CASE N-47

-1000 INTRODUCTION

Add:

N-1200 Structural Evaluation Program. To facilitate the orderly review and certification of the Design Report, a Structural Evaluation Plan (SEP) shall be included in the manufacturer's proposal to the owner. The SEP shall provide a description of the methods of analysis which the manufacturer contemplates using in various phases of the structural analysis. The plan shall indicate the degree to which the manufacturer anticipates using elastic, simplified inelastic and more detailed inelastic methods of analysis in design iterations and for demonstrating compliance with the requirements of this standard. The manufacturer shall identify any computer programs to be used, describe the basic theory of the programs, and identify the assumptions involved

in their use. The manufacturer shall also describe the extent to which the computer programs have been verified, or will be verified, and the extent to which they have been qualified for applications comparable to those involved in the proposed project.

As the design analysis progresses, the manufacturer shall provide the owner with an updated SEP and interim design analysis reports which document stress calculations in support of conclusions that the design shown by drawings used, or to be used, complies with the requirements of this standard and the ASME Code; or, when it is concluded that the requirements have not been met by the design analyzed, the manufacturer shall provide data concerning any redesign proposed, the additional analysis methods proposed for use in further analysis, or both. NE F 9-5T provides a complete description of the contents and use of the SEP.

-3000 DESIGN

-3100 General Requirements for Design.

-3110 Scope, Acceptability and Loading Conditions.

-3114 Load Histogram.

Add:

N-3114.3 Time Sequence and Duration. In the event the design specification does not include the time sequence and duration of each Level A, B, and C Service Event, agreement shall be established between the owner and manufacturer on the time sequence and duration; this agreement shall be documented in a revised Design Specification.

-3200 Design by Analysis.

-3210 Design Criteria.

-3214 Stress Analysis.

A-3214.3 Mechanical Properties. Add: Material properties from the following sources may be used without the prior approval of the owner:

- (1) ASME Code, Case N-47 and Section III.
- (2) TID-26666, for data not contained in (1) above.

If the necessary data are not available from the above sources or if the values given therein are not appropriate for the intended use, the specific values judged by the manufacturer to accurately represent the subject material shall be approved by the owner prior to use.

Recommendations, technical bases, and design implications of the proposed material properties shall be provided for the owner's consideration.

Add:

N-3214.4 Material Properties for Inelastic Analysis. The use of inelastic analysis is permitted for the purpose of determining the structural response of a component as an initial step in evaluating the creep-fatigue damage, the accumulated inelastic strain, the functional integrity, or the potential for buckling. When inelastic analysis is used in preparation for a creep-fatigue or inelastic strain evaluation, the plasticity and thermal creep properties used in the analysis shall be average (or representative). It is intended that the results of analysis based on "average" properties be compared to the Code supplied stress-rupture and fatigue limits.

N-3214.5 Fabrication and Environmental Effects. The limits of Code Case N-47 are based on tensile, creep, stress-rupture, and fatigue tests performed in air. The effects of other environments and fabrication processes on materials behavior, when significant, shall be accounted for in all structural and functional evaluations.

(a) The environmental factors which may modify material behavior include:

- (1) The environmental fluid (e.g., sodium, inert gas, air and vacuum).
- (2) The exposure to elevated temperature for long-time durations.
- (3) Irradiation.

(b) Possible effects of these factors include:

- (1) Aging.
- (2) Irradiation-induced loss of ductility.
- (3) Loss of alloying elements (including N, C, B, Mn) on both local and an overall basis.
- (4) Loss of surface material due to erosion, corrosion, or oxidation.
- (5) Alternation of the microstructure, especially at the surface of the component.

As an aid to the manufacturer, NE F 9-5T contains some information on the effects of environment upon structural integrity. The SEP shall describe the degree and scope of the fabrication and environmental effect considerations which will be implemented in each stage of the design analysis.

-3220 Design Rules and Limits for Load-Controlled Stresses in Structures Other than Bolts.

-3225 Level D Service Limits. Add:

N-3225(f) When the stress ratio methods of Appendix F are utilized the designer shall consider any significant distortion, warping or ovalization, of the cross-section. In materials which have a low yield to ultimate strength ratio, and also high elongation, the effects of cross-sectional distortion may significantly reduce the load carrying capacity below the values predicted by the stress ratio method.

-3230 Stress Limits for Load-Controlled Stresses on Bolts.

-3231 General Requirements.

A-3231(a) Change to read:

"(a) When bolts in elevated temperature components are not exposed to elevated temperature service, they may be designed using ..."

-3240 Special Requirements for Elevated Temperature Components.

-3241 Nonductile Fracture. Add:

N-3241(c) The procedure given below may be used to determine whether further consideration of nonductile fracture is required.

1. Develop a J- Δa fracture toughness test record, where J is the value of the J-integral and Δa is the crack growth, for the material, product form, prior service conditions, and temperature of interest. Fit to the post-initiation portion of the test record a power-law model of the form

$$J = \Psi (\Delta a)^\gamma$$

where Ψ and γ are empirical values.

2. Calculate a_D , an estimated unstable crack size, from

$$a_D = \frac{E\Psi}{\sigma_o^2} \left(\frac{\gamma b}{\omega} \right)^\gamma$$

where E is the elastic modulus and σ_o is the flow stress (defined to be the average of the yield strength and the tensile strength) for the material and temperature of interest. The length parameter b is defined to be one inch and the dimensionless scale parameter $_$ is defined to be five.

3. If the calculated value of a_D is greater than twenty-five inches, unstable crack growth is regarded as so unlikely that further consideration of this failure mode is not required. If the value of a_D does not exceed twenty-five inches, unstable crack growth is not necessarily likely, but further consideration of the failure mode is required.

-3250 Limits on Deformation - Controlled Quantities.

Add:

N-3253 Creep-Fatigue Interaction Test.

There is a small chance that the creep-fatigue life of a given heat of austenitic stainless steel will be substantially less than that upon which the rules of this Case are based. Thus when the service conditions for Levels A, B, and C do not satisfy the limits of both T-1325(a) and T-1325(b) a creep-fatigue interaction test of each lot* of material shall be performed to obtain information about the creep-fatigue interaction properties of that lot. One creep-fatigue interaction test shall be performed in air at 1100°F (593°C) at a strain range of 1.0% with a one-hour hold period at the maximum positive strain in each cycle. The test shall be continued until the specimen fractures, develops significant cracks, encounters a significant (about 20%) load range drop, or exceeds the reference cyclic life, whichever occurs first. For type 304 austenitic stainless steel the reference cyclic life is 214 cycles. For type 316 austenitic stainless steel and Alloy 800H the reference cyclic lives are to be determined. When a lot of material does not meet this limit, the Owner shall be notified prior to using that material.

-3300 Vessel Design.

-3350 Design of Welded Construction.

*A lot is a unique combination of heat, product form, product size, and heat treatment.

-3352 Permissible Types of Welded Joints. Add:

N-3352(i) Joint designs having internal crevices, such as retained backing strips or socket welds, shall not be used for components intended for liquid metal service unless the prior written approval of the owner is obtained for each application.

APPENDIX I-14, TABLES I-14.0

Table I-14.1: Permissible Materials for Structures Other than Bolting.

Add a note that applies to type 304 and 316 stainless steel:

Note 7 - Paragraph -3253 imposes a creep-fatigue interaction test for all lots of austenitic stainless steel used above certain time-at-temperature limits.

APPENDIX T RULES FOR STRAIN, DEFORMATION, AND FATIGUE LIMITS AT ELEVATED TEMPERATURES

T-1300 DEFORMATION AND STRAIN LIMITS FOR STRUCTURAL INTEGRITY

T-1320 Satisfaction of Strain Limits Using Elastic Analysis.

AT-1321 General Requirements. Modify the fourth line to read: "T-1323, T-1324, AT-1325, or NT-1327 satisfied."

Modify the last sentence of the first paragraph to read: "... be evaluated in T-1322, T-1323, T-1324, AT-1325, and NT-1327."

AT-1321(b) modify the last line to read: "...using Eq. (6) of -3223."

AT-1321(c) Modify the first sentence to read: "...of T-1322, T-1323, T-1324, AT-1325, or NT-1327, whichever ..."

Modify the second sentence to read: "Note that T-1324, and NT-1327 provide for ..."

AT-1321(d) Modify the second line to read: "satisfy the conditions of T-1322, T-1323, or AT-1325."

Modify the second sentence to read: "T-1324 and NT-1327 provide methods for ..."

Modify the last sentence to read: "... of T-1322, T-1323, or AT-1325."

AT-1321(e) Modify the first sentence to read: "The time and temperature conditions used in selecting the isochronous curves in T-1324 or NT-1327 shall always sum to the entire life regardless of whether all or only part of the cycles are evaluated under the procedures of T-1324 or NT-1327."

T-1324 Test No. 3.

AT-1324(a) Modify the first sentence to read: "...the criteria of T-1322, T-1323, or AT-1325 may be ..."

AT-1325 Test No. 4.

Modify the last line of the first paragraph to read: "(a) through (e) (below), or the requirements of (f) (below), are satisfied."

AT-1325(d) Add:

The value of $1.5 S_m$ should be evaluated at the cold extreme of the thermal stress cycle.

Add:

AT-1325(f) The requirements of (a) through (e) above are satisfied using 1.5 times the average* yield strength (instead of 1.5 times the tabulated** yield strength) in (a), and using 1.20 times the average yield strength (instead of 1.25 times the tabulated yield strength) in (b), and the modified $3S_m$ limit of (d) is used in NB-3222.2 and NB-3222.3. In this case the rules of NB-3228.5 may be used with the temperature limit of 800°F (427°C) replaced by 1300°F (704°C) and with $3S_m$ replaced by the modified $3S_m$ of (d).

T-1326 Special Requirements for Piping Components.

AT-1326(b) Modify the next to last line to read: "... and $\bar{S}_m$ is the lessor of..."

*The phrase "average yield strengths" as used here, is the mean of all yield strength values for the material/heat treatment/temperature combination of interest. The range of possible heat treatments includes: mill annealed, stress relieved, aged, and re-solution annealed. The Nuclear System Materials Handbook contains estimates of this average yield strength for at least one of the heat treatments of most of the materials used in elevated temperature Class 1 construction. The yield strength is the 0.2% offset value from a static test of a uniaxially loaded tensile specimen.

**Table I-14.5 of Code Case N-47.

Add:

NT-1327 Test No. 5. For axisymmetric structures subject to axisymmetric loading away from local structural discontinuities (as defined in paragraph -3213.3) the complete relaxation procedure of subsection 6.3.1.2 of NE F 9-5T may be used to bound the accumulated inelastic strains. If the resulting bounds on membrane and surface strains do not exceed the limits of T-1310 (a) and (b), respectively, the strain limits of T-1310 are considered satisfied.

T-1400 CREEP-FATIGUE EVALUATION

T-1410 General Requirements.

AT-1411 Damage Equation. In the definition of " T_d " modify the first sentence to read: "=allowable time duration at a given peak stress intensity (for elastic analysis) or at a given peak effective stress (for inelastic analysis) of load condition k." Add:

Peak stress effects (creep-rupture damage due to peak stresses) have been included in the Fig. T-1430 design fatigue curves. Thus, the primary-plus-secondary stress values (rather than the primary-plus-secondary-plus-peak values) may be used to determine the creep damage when Fig. T-1430 is used in the fatigue evaluation.

T-1420 Limits Using Inelastic Analysis. Add:

NT-1420(d) Where local discontinuities are analytically modeled, the analysis shall demonstrate the ability of the model to determine the local stress and strain. Otherwise, the fatigue damage sum shall be evaluated by using Eq. 7 to obtain the strain range and by entering the fatigue design curve, Fig. T-1430.

T-1430 Limits Using Elastic Analysis.

T-1432 Fatigue Damage Evaluation. Add the following after Table T-1430-1C:

Table NT-1430-1D

Design Fatigue Strain Range, ϵ_t , for 2-1/4 Cr - 1 Mo
(Elastic Analysis)

Design Life: 100 h				
N_d	ϵ_t , strain range (in./in.) at temperature			
Number of Cycles	427°C (800°F)	482°C (900°F)	538°C (1000°F)	593°C (1100°F)
10^1	0.0145	0.0105	0.0074	0.0074
2×10^1	0.0110	0.0071	0.0045	0.0026
4×10^1	0.0090	0.0054	0.0032	0.00155
10^2	0.0072	0.0041	0.0023	0.0011
2×10^2	0.0062	0.00345	0.0019	0.00094
4×10^2	0.0053	0.0030	0.0017	0.00086
10^3	0.0044	0.0025	0.0015	0.00080
2×10^3	0.00365	0.00218	0.00138	0.00079
4×10^3	0.0031	0.0019	0.0013	0.00078
10^4	0.0025	0.0017	0.00122	0.000775

Fig. NT-1430-1D. Design fatigue strain range ϵ_t for
2-1/4 Cr - 1 Mo -- Elastic Analysis

Table NT-1430-1D

Design Fatigue Strain Range, ϵ_t , for 2-1/4 Cr - 1 Mo
(Elastic Analysis)

N_d Number of Cycles	Design Life: 1000 h ϵ_t , strain range (in./in.) at temperature		
	427°C (800°F)	482°C (900°F)	538°C (1000°F)
10^1	0.0126	0.0080	0.0051
2×10^1	0.0085	0.0056	0.00245
4×10^1	0.0064	0.0042	0.00163
10^2	0.0049	0.0033	0.00128
2×10^2	0.0040	0.0028	0.00119
4×10^2	0.0035	0.0024	0.0011
10^3	0.0030	0.0021	0.00103
2×10^3	0.0026	0.0019	0.0010
4×10^3	0.00235	0.0017	0.00098
10^4	0.0021	0.0015	0.00095
2×10^4	0.0019	0.0014	0.00094
4×10^4	0.0018	0.0013	0.00093
10^5	0.00161	0.0012	0.00092

Fig. NT-1430-1D. Design fatigue strain range ϵ_t for
2-1/4 Cr -- Mo -- Elastic Analysis.

Table NT-1430-1D

Design Fatigue Strain Range, ϵ_t , for 2-1/4 Cr - 1 Mo
(Elastic Analysis)

N_d Number of Cycles	Design Life: 10,000 h ϵ_t , strain range (in./in.) at temperature		
	427°C (800°F)	482°C (900°F)	538°C (1000°F)
10^1	0.0098	0.0038	0.0037
2×10^1	0.0070	0.0027	0.00175
4×10^1	0.0053	0.0021	0.00118
10^2	0.0039	0.00166	0.00090
2×10^2	0.0032	0.0015	0.00082
4×10^2	0.00275	0.0014	0.00079
10^3	0.0023	0.0013	0.00076
2×10^3	0.0020	0.00123	0.00073
4×10^3	0.00184	0.0012	0.00071
10^4	0.0017	0.00115	0.00070
2×10^4	0.0016	0.0011	0.000695
4×10^4	0.0015	0.00108	0.00069
10^5	0.0014	0.00102	0.00068
2×10^5	0.00133	0.00102	0.00068
4×10^5	0.0013	0.0010	0.00068
10^6	0.00123	0.0010	0.00068

Fig. NT-1430-1D. Design fatigue strain range ϵ_t for
2-1/4 Cr -- Mo -- Elastic Analysis.

Table NT-1430-1D

Design Fatigue Strain Range, ϵ_t , for 2-1/4 Cr - 1 Mo
(Elastic Analysis)

N _d Number of Cycles	Design Life: 80,000 h ϵ_t , strain range (in./in.) at temperature		
	427°C (800°F)	482°C (900°F)	538°C (1000°F)
10 ¹	0.0047	0.00206	0.00202
2 x 10 ¹	0.0032	0.0015	0.0014
4 x 10 ¹	0.0025	0.00122	0.00102
10 ²	0.00202	0.00106	0.00080
2 x 10 ²	0.00185	0.0010	0.00070
4 x 10 ²	0.00173	0.00097	0.00063
10 ³	0.0016	0.00094	0.00056
2 x 10 ³	0.00156	0.00093	0.00054
4 x 10 ³	0.0015	0.00091	0.00052
10 ⁴	0.00143	0.00090	0.00051
2 x 10 ⁴	0.0014	0.00089	0.00051
4 x 10 ⁴	0.00132	0.00088	0.00051
10 ⁵	0.0013	0.00087	0.00050
2 x 10 ⁵	0.00122	0.00086	0.00050
4 x 10 ⁵	0.0012	0.00085	0.00050
10 ⁶	0.00119	0.00084	0.00050

Fig. NT-1430-1D. Design fatigue strain range ϵ_t for
2-1/4 Cr - 1 Mo -- Elastic Analysis.

Table NT-1430-1D

Design Fatigue Strain Range, ϵ_t , for 2-1/4 Cr - 1 Mo
(Elastic Analysis)

N_d Number of Cycles	Design Life: 250,000 h ϵ_t , strain range (in./in.) at temperature		
	427°C (800°F)	482°C (900°F)	538°C (1000°F)
10^1	0.0022	0.00152	0.00148
2×10^1	0.0020	0.00122	0.0011
4×10^1	0.00182	0.00103	0.00089
10^2	0.0017	0.00090	0.00070
2×10^2	0.0016	0.00084	0.00062
4×10^2	0.00152	0.00081	0.00056
10^3	0.00145	0.00080	0.00050
2×10^3	0.0014	0.00079	0.00048
4×10^3	0.00133	0.00078	0.00046
10^4	0.0013	0.000775	0.00045
2×10^4	0.00123	0.00077	0.00045
4×10^4	0.00121	0.00077	0.00045
10^5	0.00119	0.00076	0.00045
2×10^5	0.00113	0.00076	0.00045
4×10^5	0.00111	0.00085	0.00045
10^6	0.0011	0.00076	0.00045

Fig. NT-1430-1D Design fatigue strain range ϵ_t for
2-1/4 Cr - 1 Mo -- Elastic Analysis.

T-1435 Alternate Creep Fatigue Evaluation. Add:

AT-1435(d) The rules of NB-3228.5, with temperature limits limits of 700°F (371°C) and 800°F (427°C) replaced by 1200°F (649°C) and 1300°F (704°C), respectively, and with $3S_m$ replaced by the modified $3S_m$ of AT-1325(d), may be used for the materials of Table I-14.1 provided that AT-1325(f) is also used.

AT-1435(e) The references to NB-3222 and NB-3227 in NB-3222.4(e) shall be replaced by references to -3222 and -3227 respectively.

Add:

NT-1440 Alternative Limits for Thermal Stripping. The requirements of T-1400 may be satisfied by meeting all of the requirements of T-1441, and any of the requirements of T-1442, at every point of interest in the component.

NT-1441 General Requirements. Each of the following shall be satisfied:

- (1) The material shall be type 316 stainless steel with a grain size of ASTM 3.2 or finer.
- (2) If the point being considered is on the surface of the component, it shall be bathed in sodium.
- (3) The only significant loading shall be due to thermal striping.
- (4) The maximum metal temperature during the thermal striping portion of the specified service life shall not exceed 1100°F (593°C).
- (5) The frequency of the thermal cycles shall exceed 0.1 Hz.

NT-1442 Service-Specific Requirements. One of the following shall be satisfied:

- (1) The maximum fluid (or metal) temperature range for all thermal striping cycles during the specified service life shall not exceed 70°F (21°C).
- (2) The maximum fluid (or metal) temperature range for all thermal striping cycles during the specified service life shall not exceed the allowable temperature range obtained from Figure or Table NT-1440-1 for the given number of all thermal striping cycles during the specified service life, for the given maximum metal temperature during the thermal striping portion of the service life, and for the given maximum grain size.

- (3) The maximum value of the equivalent elastic-plastic strain range for all thermal striping cycles during the specified service life shall not exceed the allowable strain range obtained from Figure or Table NT-1440-2 for the given number of all thermal striping cycles during the specified service life, for the given maximum metal temperature during the thermal striping portion of the service life, and for the given maximum grain size. The equivalent elastic-plastic strain range is defined as

$$\Delta\epsilon_{eq}^{EP} = \Delta\epsilon_{eq}^E + \Delta\epsilon_{eq}^P$$

where,

$$\Delta\epsilon_{eq}^E = \frac{\sqrt{2}}{2(1+\nu)} \sqrt{(\Delta\epsilon_1^E - \Delta\epsilon_2^E)^2 + (\Delta\epsilon_2^E - \Delta\epsilon_3^E)^2 + (\Delta\epsilon_3^E - \Delta\epsilon_1^E)^2}$$

$$\Delta\epsilon_{eq}^P = \frac{\sqrt{2}}{3} \sqrt{(\Delta\epsilon_1^P - \Delta\epsilon_2^P)^2 + (\Delta\epsilon_2^P - \Delta\epsilon_3^P)^2 + (\Delta\epsilon_3^P - \Delta\epsilon_1^P)^2}$$

$$\Delta\epsilon_i^E = \epsilon_{i,max}^E - \epsilon_{i,min}^E, \text{ and } \Delta\epsilon_i^P = \epsilon_{i,max}^P - \epsilon_{i,min}^P \quad (i=1,2,3).$$

ϵ_i^E and ϵ_i^P represent principal components of elastic and plastic strain respectively. The subscripts "max" and "min" refer to points in a thermal striping strain cycle that result in a maximum value of $\Delta\epsilon_{eq}^{EP}$ for that cycle.

- (4) The sum of n/N values shall not exceed a value of one, where n is the actual number of thermal striping cycles with a given combination of strain range (equal to $\Delta\epsilon_{eq}^{EP}$, defined above) and maximum metal temperature (during the cycle), and N is the allowable number of such cycles obtained from Figure or Table NT-1440-2. The summation is to be carried out for all combinations of strain range and maximum metal temperature during the thermal striping portion of the service life.

Table NT-1440-1

Allowable Thermal Striping Temperature Range for 316 Stainless Steel

Temperature Range in °C (°F) for Given
Maximum Temperature and Grain Size

Number of Cycles, N	ASTM 3.2		ASTM 3.2		ASTM 5.0	
	482°C	(900°F)	593°C	(1100°F)	593°C	(1100°F)
10^2	405.0	(761.0)	347.0	(656.0)	354.0	(669.0)
2×10^2	301.0	(573.0)	261.0	(502.0)	268.0	(515.0)
5×10^2	214.0	(418.0)	189.0	(373.0)	197.0	(386.0)
10^3	173.0	(343.0)	154.0	(309.0)	162.0	(323.0)
2×10^3	143.0	(290.0)	129.0	(264.0)	137.0	(278.0)
5×10^3	117.0	(243.0)	106.0	(223.0)	113.0	(236.0)
10^4	101.0	(214.0)	89.4	(193.0)	93.9	(201.0)
2×10^4	83.3	(182.0)	75.0	(167.0)	79.4	(175.0)
5×10^4	67.8	(154.0)	61.7	(143.0)	65.6	(150.0)
10^5	60.0	(140.0)	54.4	(130.0)	58.3	(137.0)
2×10^5	53.9	(129.0)	48.9	(120.0)	52.8	(127.0)
5×10^5	47.8	(118.0)	43.3	(110.0)	47.2	(117.0)
10^6	44.4	(112.0)	40.6	(105.0)	44.4	(112.0)
2×10^6	41.7	(107.0)	37.8	(100.0)	42.2	(108.0)
5×10^6	38.9	(102.0)	35.3	(95.6)	39.4	(103.0)
10^7	37.3	(99.1)	33.3	91.9	38.3	(101.0)
2×10^7	35.9	(96.7)	31.6	88.9	36.9	(98.4)
5×10^7	34.1	(93.4)	29.8	85.7	35.4	(95.8)
10^8	32.9	(91.3)	28.8	83.8	34.3	(93.8)
2×10^8	32.0	(89.6)	27.8	82.1	33.4	(92.2)
5×10^8	30.9	(87.7)	26.8	80.3	32.4	(90.4)
10^9	30.3	(86.5)	26.2	79.2	31.8	(89.3)

Fig. NT-1440-1. Allowable thermal stripping temperature range, for given maximum temperature, for type 316 stainless steel with grain size of ASTM 3.2 or finer.

Table NT-1440-2

Allowable Thermal Striping Strain Range For Type 316 Stainless Steel

Strain Range (%) for Given
Maximum Temperature and Grain Size

Number of Cycles, N	482°C (900°F) ASTM 3.2	593°C (1100°F) ASTM 3.2	593°C (1100°F) ASTM 5.0
10^2	1.587	1.398	1.427
2×10^2	1.182	1.058	1.087
5×10^2	0.8522	0.7765	0.8055
10^3	0.6935	0.6387	0.6677
2×10^3	0.5820	0.5406	0.5696
5×10^3	0.4807	0.4503	0.4793
10^4	0.4188	0.3851	0.4021
2×10^4	0.3500	0.3246	0.3416
5×10^4	0.2878	0.2692	0.2862
10^5	0.2548	0.2395	0.2565
2×10^5	0.2300	0.2169	0.2339
5×10^5	0.2059	0.1947	0.2117
10^6	0.1924	0.1821	0.1991
2×10^6	0.1816	0.1720	0.1890
5×10^6	0.1707	0.1617	0.1787
10^7	0.1643	0.1555	0.1725
2×10^7	0.1590	0.1504	0.1674
5×10^7	0.1535	0.1450	0.1620
10^8	0.1501	0.1417	0.1587
2×10^8	0.1472	0.1387	0.1559
5×10^8	0.1442	0.1359	0.1529
10^9	0.1422	0.1340	0.1510

Fig. NT-1440-2. Allowable thermal striping strain range for type 316 stainless steel for given maximum temperature and grain size of ASTM 3.2.

END

DATE
FILMED

5/04/93