2/16/92 (Jan-1)

ORNL/TM-11948

**OAK RIDGE
NATIONAL
LABORATORY**

MARTIN MARIETTA

A Comprehensive Review of the XRD Data
of the Primary and Secondary Phases Present
in the BSCCO Superconductor System

(Part I: Ca-Sr-Cu Oxides)

Brian J. Reardon
Camden R. Hubbard

MANAGED BY
MARTIN MARIETTA ENERGY SYSTEMS, INC.
FOR THE UNITED STATES
DEPARTMENT OF ENERGY

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Metals and Ceramics Division

**A COMPREHENSIVE REVIEW OF THE XRD DATA OF THE
PRIMARY AND SECONDARY PHASES PRESENT IN
THE BSCCO SUPERCONDUCTOR SYSTEM
(Part I: Ca-Sr-Cu OXIDES)**

Brian J. Reardon
Camden R. Hubbard

Date Published - January 1992

NOTICE: This document contains information of a preliminary nature.
It is subject to revision or correction and therefore does not
represent a final report.

Prepared for
U.S. Department of Energy
Assistant Secretary for Conservation and Renewable Energy
Office of Transportation Technologies
AK 06 00 00 0

Prepared by the
OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee 37831-6285
managed by
MARTIN MARIETTA ENERGY SYSTEMS, INC.
for the
U.S. DEPARTMENT OF ENERGY
under contract DE-AC05-84OR21400

MASTER

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES	v
LIST OF TABLES	vii
ABSTRACT	1
1. INTRODUCTION	1
2. REVIEW PROCEDURE	2
3. RESULTS AND DISCUSSION	4
3.1 (Ca,Sr)O	5
3.2 (Ca,Sr) ₂ CuO ₃	7
3.3 (Ca,Sr) ₁₄ Cu ₂₄ O ₄₁	9
3.4 (Ca,Sr)CuO ₂	13
3.5 (Ca,Sr)Cu ₂ O ₃	16
3.6 (Ca,Sr)Cu ₂ O ₂	18
4. CONCLUSIONS	19
5. ACKNOWLEDGMENTS	19
6. REFERENCES	21
APPENDIX A. (Ca,Sr)O	25
APPENDIX B. (Ca,Sr) ₂ CuO ₃	32
APPENDIX C. (Ca,Sr) ₁₄ Cu ₂₄ O ₄₁	54
APPENDIX D. (Ca,Sr)CuO ₂	63
APPENDIX E. Ca _{0.14} Sr _{0.86} CuO ₂	73
APPENDIX F. (Ca,Sr)Cu ₂ O ₃	75
APPENDIX G. (Ca,Sr)Cu ₂ O ₂	80

LIST OF FIGURES

<u>Figure</u>	<u>Page</u>
1 Simulated XRD plots of $\text{Ca}_{2-x}\text{Sr}_x\text{CuO}_3$ for $x = 0, 0.5, 1.0, 1.5, 2.0$	2

LIST OF TABLES

<u>Table</u>	<u>Page</u>
1 Nomenclature used in this report	3
2 MICRO-POWD calculation parameters	4
3 (Ca,Sr)O crystallographic parameters	5
4 (Ca,Sr)O cell parameter (a), D_x , and I/I_c	5
5 Three major lines of simulated (Ca,Sr)O and PDF cards 37-1497 (CaO), 23-127 ($\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$), and 6-520 (SrO)	6
6 (Ca,Sr) $_2\text{CuO}_3$ crystallographic parameters	7
7 (Ca,Sr) $_2\text{CuO}_3$ unit cell parameters (a), D_x , and I/I_c	8
8 Three major lines of simulated Ca_2CuO_3 , CaSrCuO_3 , Sr_2CuO_3 , and PDF cards: 34-282 (Ca_2CuO_3) and 34-283 (Sr_2CuO_3)	9
9 (Ca,Sr) $_{14}\text{Cu}_{24}\text{O}_{41}$ crystallographic parameters	10
10 (Ca,Sr) $_{14}\text{Cu}_{24}\text{O}_{41}$ unit cell parameters, D_x , and I/I_c	11
11 Three major lines of simulated $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_3\text{Sr}_{11}\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_5\text{Sr}_9\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_7\text{Sr}_7\text{Cu}_{24}\text{O}_{41}$, observed $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ and PDF cards 39-489 ($\text{Sr}_{1.75}\text{Cu}_3\text{O}_{5.13}$) and 39-250 (SrCu_2O_3)	12
12 (Ca,Sr) $_2\text{CuO}_2$ crystallographic parameters	13
13 (Ca,Sr) CuO_2 and $\text{Ca}_{0.86}\text{Sr}_{0.14}\text{CuO}_2$ unit cell parameters, D_x , and I/I_c	14
14 Three main peaks of simulated SrCuO_2 , $\text{Ca}_{0.3}\text{Sr}_{0.7}\text{CuO}_2$, $\text{Ca}_{0.25}\text{Sr}_{0.75}\text{CuO}_2$, and PDF cards: 39-1492 (SrCuO_2) and 38-1179 (SrCuO_2)	14
15 Four main peaks of tetragonal $\text{Ca}_{0.86}\text{Sr}_{0.14}\text{CuO}_2$	15
16 Four main peaks for observed CaCuO_2	16
17 (Ca,Sr) Cu_2O_3 crystallographic parameters and I/I_c (for all four models: $a = 9.942$; $b = 4.0786$; $c = 3.459$; $D_x = 5.094$)	16
18 Three strongest lines for the four different structure models of CaCu_2O_3 presented by Hoppe and PDF card 34-284 (CaCu_2O_3)	17
19 SrCu_2O_2 crystallographic parameters	18
20 SrCu_2O_2 unit cell parameters, D_x , and I/I_c	18
21 Three main peaks of SrCu_2O_2 and PDF card 38-1178 (SrCu_2O_2)	19
A.1 Simulated X-ray powder pattern for CaO	26
A.2 Simulated X-ray powder pattern for $\text{Ca}_{0.9}\text{Sr}_{0.1}\text{O}$	26

<u>Table</u>	<u>Page</u>
A.3 Simulated X-ray powder pattern for $\text{Ca}_{0.8}\text{Sr}_{0.2}\text{O}$	27
A.4 Simulated X-ray powder pattern for $\text{Ca}_{0.7}\text{Sr}_{0.3}\text{O}$	27
A.5 Simulated X-ray powder pattern for $\text{Ca}_{0.6}\text{Sr}_{0.4}\text{O}$	28
A.6 Simulated X-ray powder pattern for $\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$	28
A.7 Simulated X-ray powder pattern for $\text{Ca}_{0.4}\text{Sr}_{0.6}\text{O}$	29
A.8 Simulated X-ray powder pattern for $\text{Ca}_{0.3}\text{Sr}_{0.7}\text{O}$	29
A.9 Simulated X-ray powder pattern for $\text{Ca}_{0.2}\text{Sr}_{0.8}\text{O}$	30
A.10 Simulated X-ray powder pattern for $\text{Ca}_{0.1}\text{Sr}_{0.9}\text{O}$	30
A.11 Simulated X-ray powder pattern for SrO	31
B.1 Simulated X-ray powder pattern for Ca_2CuO_3	33
B.2 Simulated X-ray powder pattern for $\text{Ca}_{1.9}\text{Sr}_{0.1}\text{CuO}_3$	34
B.3 Simulated X-ray powder pattern for $\text{Ca}_{1.8}\text{Sr}_{0.2}\text{CuO}_3$	35
B.4 Simulated X-ray powder pattern for $\text{Ca}_{1.7}\text{Sr}_{0.3}\text{CuO}_3$	36
B.5 Simulated X-ray powder pattern for $\text{Ca}_{1.6}\text{Sr}_{0.4}\text{CuO}_3$	37
B.6 Simulated X-ray powder pattern for $\text{Ca}_{1.5}\text{Sr}_{0.5}\text{CuO}_3$	38
B.7 Simulated X-ray powder pattern for $\text{Ca}_{1.4}\text{Sr}_{0.6}\text{CuO}_3$	39
B.8 Simulated X-ray powder pattern for $\text{Ca}_{1.3}\text{Sr}_{0.7}\text{CuO}_3$	40
B.9 Simulated X-ray powder pattern for $\text{Ca}_{1.2}\text{Sr}_{0.8}\text{CuO}_3$	41
B.10 Simulated X-ray powder pattern for $\text{Ca}_{1.1}\text{Sr}_{0.9}\text{CuO}_3$	42
B.11 Simulated X-ray powder pattern for CaSrCuO_3	43
B.12 Simulated X-ray powder pattern for $\text{Ca}_{0.9}\text{Sr}_{1.1}\text{CuO}_3$	44
B.13 Simulated X-ray powder pattern for $\text{Ca}_{0.8}\text{Sr}_{1.2}\text{CuO}_3$	45
B.14 Simulated X-ray powder pattern for $\text{Ca}_{0.7}\text{Sr}_{1.3}\text{CuO}_3$	46
B.15 Simulated X-ray powder pattern for $\text{Ca}_{0.6}\text{Sr}_{1.4}\text{CuO}_3$	47
B.16 Simulated X-ray powder pattern for $\text{Ca}_{0.5}\text{Sr}_{1.5}\text{CuO}_3$	48
B.17 Simulated X-ray powder pattern for $\text{Ca}_{0.4}\text{Sr}_{1.6}\text{CuO}_3$	49
B.18 Simulated X-ray powder pattern for $\text{Ca}_{0.3}\text{Sr}_{1.7}\text{CuO}_3$	50
B.19 Simulated X-ray powder pattern for $\text{Ca}_{0.2}\text{Sr}_{1.8}\text{CuO}_3$	51
B.20 Simulated X-ray powder pattern for $\text{Ca}_{0.1}\text{Sr}_{1.9}\text{CuO}_3$	52
B.21 Simulated X-ray powder pattern for Sr_2CuO_3	53
C.1 Simulated X-ray powder pattern for $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$	55
C.2 Simulated X-ray powder pattern for $\text{Sr}_{13}\text{CaCu}_{24}\text{O}_{41}$	56
C.3 Simulated X-ray powder pattern for $\text{Sr}_{12}\text{Ca}_2\text{Cu}_{24}\text{O}_{41}$	57
C.4 Simulated X-ray powder pattern for $\text{Sr}_{11}\text{Ca}_3\text{Cu}_{24}\text{O}_{41}$	58

<u>Table</u>	<u>Page</u>
C.5 Simulated X-ray powder pattern for $\text{Sr}_{10}\text{Ca}_4\text{Cu}_{24}\text{O}_{41}$	59
C.6 Simulated X-ray powder pattern for $\text{Sr}_9\text{Ca}_5\text{Cu}_{24}\text{O}_{41}$	60
C.7 Simulated X-ray powder pattern for $\text{Sr}_8\text{Ca}_6\text{Cu}_{24}\text{O}_{41}$	61
C.8 Simulated X-ray powder pattern for $\text{Sr}_7\text{Ca}_7\text{Cu}_{24}\text{O}_{41}$	62
D.1 Simulated X-ray powder pattern for SrCuO_2	64
D.2 Simulated X-ray powder pattern for $\text{Sr}_{0.9}\text{Ca}_{0.1}\text{CuO}_2$	65
D.3 Simulated X-ray powder pattern for $\text{Sr}_{0.8}\text{Ca}_{0.2}\text{CuO}_2$	66
D.4 Simulated X-ray powder pattern for $\text{Sr}_{0.7}\text{Ca}_{0.3}\text{CuO}_2$	67
D.5 Simulated X-ray powder pattern for $\text{Sr}_{0.6}\text{Ca}_{0.4}\text{CuO}_2$	68
D.6 Simulated X-ray powder pattern for $\text{Sr}_{0.5}\text{Ca}_{0.5}\text{CuO}_2$	69
D.7 Simulated X-ray powder pattern for $\text{Sr}_{0.4}\text{Ca}_{0.6}\text{CuO}_2$	70
D.8 Simulated X-ray powder pattern for $\text{Sr}_{0.3}\text{Ca}_{0.7}\text{CuO}_2$	71
D.9 Simulated X-ray powder pattern for $\text{Sr}_{0.25}\text{Ca}_{0.75}\text{CuO}_2$	72
E.1 Simulated X-ray powder pattern for $\text{Ca}_{0.14}\text{Sr}_{0.86}\text{CuO}_2$	74
F.1 Simulated X-ray powder pattern for CaCu_2O_3 Model 1	76
F.2 Simulated X-ray powder pattern for CaCu_2O_3 Model 2	77
F.3 Simulated X-ray powder pattern for CaCu_2O_3 Model 3	78
F.4 Simulated X-ray powder pattern for CaCu_2O_3 Model 4	79
G.1 Simulated X-ray powder pattern for SrCu_2O_2	81

**A COMPREHENSIVE REVIEW OF THE XRD DATA OF THE PRIMARY
AND SECONDARY PHASES PRESENT IN THE BSCCO
SUPERCONDUCTOR SYSTEM
(Part I: Ca-Sr-Cu OXIDES)***

B. J. Reardon[†] and C. R. Hubbard[‡]

ABSTRACT

X-ray powder patterns for the phases in the CaO-SrO-CuO ternary system, along with the corresponding crystal structures, were obtained from the literature and from the Powder Diffraction File (PDF). Available X-ray diffraction (XRD) patterns were compared with each other and, when possible, with a simulated pattern for each phase, yielding a recommended reference pattern. The simulated powder patterns presented here deal with the phases found within the (Ca,Sr)O, (Ca,Sr)₂CuO₃, (Ca,Sr)₁₄Cu₂₄O₄₁, (Ca,Sr)CuO₂, (Ca,Sr)Cu₂O₃, and (Ca,Sr)Cu₂O₂ solid solution series and are recommended for the PDF.

1. INTRODUCTION

The discovery of superconductivity in the Bi-Pb-Sr-Ca-Cu-O (BSCCO) system by Maeda et al.¹ has spurred intense research in the X-ray characterization of these materials. As a consequence, significant research has been conducted in the study of the phase diagrams of these four- and five-component systems.²⁻⁸ Unfortunately, accurate X-ray powder patterns and crystallographic data for many of the minor phases present in these systems are lacking. This is especially true in the case of the solid solution series whose patterns are significantly different from the corresponding end members (see Fig. 1). The lack of corresponding reference patterns in the Powder Diffraction File (PDF) severely limits identification of these phases by X-ray diffraction (XRD). Reference XRD data for the

*Research sponsored by the U. S. Department of Energy, Assistant Secretary for Conservation and Renewable Energy, Office of Utility Technologies, Office of Energy Management/Advanced Utility Concepts - Superconducting Technology Program for Electric Systems and by the Office of Transportation Technologies as part of the High Temperature Materials Laboratory User Program, under contract DE-AC05-84OR21400 managed by Martin Marietta Energy Systems, Inc.

[†]Alfred University, Binns-Merril Hall, Alfred, New York.

[‡]Martin Marietta Energy Systems, Inc., Oak Ridge Natl. Lab., Oak Ridge, Tennessee.

BSCCO superconductor phases 2201, 2212, and 2223 were published by Matheis and Snyder.⁹ This article (part 1 of a series extensively reviewing the XRD data of the BSCCO system) focuses on the phases found in the CaO-SrO-CuO ternary system.

Fig. 1. Simulated XRD plots of $\text{Ca}_{2-x}\text{Sr}_x\text{CuO}_3$ for $x = 0, 0.5, 1.0, 1.5, 2.0$.

A complete listing of the XRD patterns for the phases and solid solutions discussed in this report are reported in Appendices A through G. Table 1 presents the definitions of the abbreviations used here.

2. REVIEW PROCEDURE

An extensive review of the CaO-SrO-CuO ternary system phases and corresponding XRD data was conducted. Data utilized in this review included that obtained from literature surveys, the PDF, and private communications. Once an adequate understanding of the possible phases, solid solution series, crystal structure, and high-temperature polymorphs

Table 1. Nomenclature used in this report

*	a rating given to powder patterns by the JCPDS, symbolizing high quality and reliability
$\Delta 2\theta$	change in 2θ
2θ	two times the angle of diffraction
2201	$\text{Bi}_2\text{Sr}_2\text{CuO}_6$
2212	$\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$
2223	$\text{Bi}_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$
a	an axis that defines a unit cell (in Å)
b	an axis that defines a unit cell (in Å)
B_{iso}	isotropic thermal parameter
BSCCO	Bi-Pb-Sr-Ca-Cu-O
c	an axis that defines a unit cell (in Å)
D	density (in g/cm^3)
d	d-spacing (in Å)
D_x	calculated density (in g/cm^3)
h k l	notation used to define crystallographic planes
I	intensity
I(DS)	relative Debye-Scherrer intensity
I(INT)	relative integrated peak intensity
I(PK)	relative peak intensity
I/I_c	intensity of the 100% peak/intensity of the 100% peak of corundum
I_{rel}	relative intensity
Nobs	number of observed peaks
Nposs	number of possible peaks
occ.	lattice site occupancy
struct.	crystallographic structure
S.G.	space group

was acquired, the patterns were simulated for all the phases (including solid solutions) using the personal computer (PC) version of MICRO-POWD.¹⁰ The parameters used in these calculations are listed in Table 2. The simulated patterns and patterns acquired from the literature search and experiments were compared. Figures of merit (FOMs) for all patterns were calculated using LSQ90, a version of the lattice parameter refinement program of Evans, Appleman, and Handwerker.¹¹ The comparisons of FOMs and simulated patterns with experimental data resulted in the suggestion of a set of recommended reference powder patterns.

Table 2. MICRO-POWD calculation parameters

-
1. Program: MICRO-POWD Version: 1.
 2. Scattering factors as provided by MICRO-POWD for: O^{2-} , Sr^{2+} , Ca^{2+} , Cu^{2+} .
 3. Anomalous scattering factors as provided by MICRO-POWD for: O, Sr, Ca, Cu.
 4. $B_{iso}(Oxygen) = 2.5$; $B_{iso}(all\ others) = 1$ unless structure reference provided thermal parameters.
 5. No incident or diffracted beam monochromators.
 6. θ compensating variable divergence slit was not selected.
 7. $CuK\alpha 1$ radiation was selected ($\lambda = 1.5405981 \text{ \AA}$).
 8. For relative peak intensities, a Cauchy profile was selected.
 9. The NBS width table provided with MICRO-POWD supplied the full width at half maximum (FWHM).
-

3. RESULTS AND DISCUSSION

The phases and solid solutions present in the CaO-SrO-CuO ternary system have been extensively studied by a number of authors.^{2-4,6,7} The phases of primary concern when synthesizing BSCCO materials are: $(Ca,Sr)O$, $(Ca,Sr)_2CuO_3$, $(Ca,Sr)_{14}Cu_{24}O_{41}$, $(Ca,Sr)CuO_2$, $Ca_{0.86}Sr_{0.14}CuO_2$, and $(Ca,Sr)Cu_2O_3$.

3.1 (Ca,Sr)O

CaO and SrO have been shown to participate in a complete solid solution series across the entire binary phase system.² Furthermore, the PDF has three cards that provide information on the (Ca,Sr)O system: 37-1497 (ref. 12) and 6-520 (ref. 13) provide powder patterns for CaO and SrO, respectively, while 23-127 (ref. 14) provides a powder pattern of the $\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$ phase in the solid solution series.

Table 3 displays the crystallographic data for CaO and SrO as used in the calculations of the simulated patterns across the solid solution series. A linear change in the cell

Table 3. (Ca,Sr)O crystallographic parameters^{12,13,15}

Struct.	S.G.	Atom	Occ. $0 < x < 1$	x	y	z
Cubic	Fm3m (225)	O(1)	4	0.5	0.5	0.5
		Ca(1)	$4-4x$	0.0	0.0	0.0
		Sr	$4x$	0.0	0.0	0.0

parameters was assumed for this solid solution series, as indicated in Table 4. Table 5 displays the simulated XRD data for the three main peaks of selected phases across the solid solution series as well as the patterns for PDF cards 37-1497 (CaO), 23-127 ($\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$), and 6-520 (SrO).

Table 4. (Ca,Sr)O cell parameter (a),^{12,13}
 D_x , and I/I_c

Phase	a	D_x	I/I_c
SrO	5.16000	5.009	7.405
$\text{Sr}_{0.9}\text{Ca}_{0.1}\text{O}$	5.12506	4.877	7.115
$\text{Sr}_{0.8}\text{Ca}_{0.2}\text{O}$	5.09012	4.739	6.823
$\text{Sr}_{0.7}\text{Ca}_{0.3}\text{O}$	5.05518	4.593	6.531
$\text{Sr}_{0.6}\text{Ca}_{0.4}\text{O}$	5.02024	4.441	6.237
$\text{Sr}_{0.5}\text{Ca}_{0.5}\text{O}$	4.98529	4.280	5.942
$\text{Sr}_{0.4}\text{Ca}_{0.6}\text{O}$	4.95036	4.111	5.646
$\text{Sr}_{0.3}\text{Ca}_{0.7}\text{O}$	4.91541	3.933	5.348
$\text{Sr}_{0.2}\text{Ca}_{0.8}\text{O}$	4.88047	3.747	5.050
$\text{Sr}_{0.1}\text{Ca}_{0.9}\text{O}$	4.84553	3.551	4.751
CaO	4.81059	3.345	4.451

Table 5. Three major lines of simulated (Ca,Sr)O
and PDF cards 37-1497 (CaO), 23-127
(Ca_{0.5}Sr_{0.5}O), and 6-520 (SrO)

	CaO		Ca _{0.5} Sr _{0.5} O		SrO	
<i>h k l</i>	<i>d</i>	<i>I</i>	<i>d</i>	<i>I</i>	<i>d</i>	<i>I</i>
1 1 1	2.777	41	2.878	71	2.97	93
2 0 0	2.405	100	2.493	100	2.58	100
2 2 0	1.700	47	1.7626	5	1.8243	55
	37-1497 CaO		23-127 Ca _{0.5} Sr _{0.5} O		6-520 SrO	
<i>h k l</i>	<i>d</i>	<i>I</i>	<i>d</i>	<i>I</i>	<i>d</i>	<i>I</i>
1 1 1	2.777	36	2.853	90	2.98	90
2 0 0	2.405	100	2.472	100	2.581	100
2 2 0	1.7009	54	1.7488	80	1.825	80
FOM	116.08		17.06		82.89	
Nobs	13		11		15	
Nposs	13		12		15	
$\Delta 2\theta$	0.009		0.054		0.012	

Appendix A lists the simulated 2θ , *d*, *h k l*, and *I* values for the entire (Ca,Sr)O solid solution series. The (111) peak displays a $\Delta 2\theta$ greater than 0.25° as the *x* in Ca_{*x*}Sr_{1-*x*}O changes by 0.1. The difference in $\Delta 2\theta$ is larger yet for the other peaks in the patterns. Such differences are much larger than the typical acceptance window used for phase identification.

The PDF pattern for CaO (37-1497) agrees well with the simulated pattern and has an excellent FOM [*F*(13) = 116.08 (0.009,13)]. Note, however, that the peak at *d* = 0.80183 should be attributed to the (442) reflection, not the (600).

The PDF pattern for SrO (6-520) does not compare as well to its calculated pattern as CaO did [*F*(15) = 82.89 (0.0121,15)]. Again, however, the peak at *d* = 0.8600 should be attributed to the (442) reflection, not the (600).

The PDF pattern for $\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$ (23-127) is not as accurate [$F(11) = 17.06$ (0.054,12)] as the two cards for the two end members. Furthermore, the calculated density on the PDF card (4.45 g/cm^3) seems to be closer to that calculated for $\text{Ca}_{0.4}\text{Sr}_{0.6}\text{O}$ (4.441 g/cm^3), not $\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$ (4.280 g/cm^3). However, if the cell parameter is changed from $4.98529 \text{ \AA}$ (the cell parameter used in the calculation assuming a linear change between the end member's cell parameters) to that of the PDF card ($a = 4.93 \text{ \AA}$), the densities seem to agree. Consequently, determining which is more accurate, PDF 23-127 or the simulated pattern, requires more study.

Except for the end member patterns, it is recommended that all nine solid solution patterns be incorporated into the PDF.

3.2 $(\text{Ca,Sr})_2\text{CuO}_3$

Like $(\text{Ca,Sr})\text{O}$, $(\text{Ca,Sr})_2\text{CuO}_3$ has been shown to display a complete solid solution series across the phase diagram with a stability temperature up to 1030°C (refs. 2,3). Unfortunately, even though solid solution phases in this system have been reported,^{4,6,7,16-25} the only reference patterns available are for the end member phases 34-282 (Ca_2CuO_3) [ref. 25] and 34-283 (Sr_2CuO_3) [ref. 24]. Table 6 displays the crystallographic data for the end member phases. These data were used to simulate the solid solution series patterns. Again, a linear change in cell parameters was assumed.

Table 6. $(\text{Ca,Sr})_2\text{CuO}_3$ crystallographic parameters^{22,23}

Struct.	S.G.	Atom	Occ. $0 < x < 1$	x	y	z
Ortho	Immm (71)	Ca	4-4x	0.15	0.0	0.5
		Sr	4x	0.15	0.0	0.5
		Cu	2	0.0	0.5	0.0
		O1	4	0.34	0.0	0.5
		O2	2	0.0	0.0	0.0

This assumption is displayed in Table 7. The resulting simulated XRD data for the three strongest lines across the solid solution series are presented in Table 8 as well as the data for card 34-282 (Ca_2CuO_3) and 34-283 (Sr_2CuO_3).

Table 7. $(\text{Ca,Sr})_2\text{CuO}_3$ unit cell parameter (a),^{24,25}
 D_x , and I/I_c

Phase Ca:Sr	a	b	c	D_x	I/I_c
2:0	12.2340	3.77690	3.25730	4.229	2.694
1.9:0.1	12.2565	3.78338	3.26922	4.303	2.775
1.8:0.2	12.2790	3.78985	3.28114	4.376	2.857
1.7:0.3	12.3015	3.79632	3.29306	4.447	2.939
1.6:0.4	12.3240	3.80280	3.30498	4.517	3.020
1.5:0.5	12.3465	3.80927	3.31690	4.586	3.102
1.4:0.6	12.3690	3.81575	3.32882	4.654	3.184
1.3:0.7	12.3915	3.22230	3.34074	4.721	3.265
1.2:0.8	12.4140	3.82870	3.35266	4.787	3.347
1.1:0.9	12.4365	3.83518	3.36458	4.852	3.429
1:1	12.4590	3.84165	3.37650	4.915	3.511
0.9:1.1	12.4815	3.84812	3.38842	4.978	3.592
0.8:1.2	12.5040	3.85460	3.40034	5.040	3.674
0.7:1.3	12.5265	3.86107	3.41226	5.100	3.756
0.6:1.4	12.5490	3.86755	3.42418	5.160	3.838
0.5:1.5	12.5715	3.87403	3.43610	5.219	3.920
0.4:1.6	12.5940	3.88050	3.44802	5.276	4.002
0.3:1.7	12.6165	3.88698	3.44599	5.333	4.084
0.2:1.8	12.6615	3.89345	3.47186	5.379	4.159
0.1:1.9	12.6615	3.89992	3.48378	5.444	4.249
0:2	12.6840	3.90640	3.49570	5.498	4.317

Table 8. Three major lines of simulated Ca_2CuO_3 , CaSrCuO_3 , Sr_2CuO_3 , and PDF cards: 34-282 (Ca_2CuO_3) and 34-283 (Sr_2CuO_3)

			Ca_2CuO_3		CaSrCuO_3		Sr_2CuO_3	
$h\ k\ \ell$	d	I	d	I	d	I	d	I
3 1 0	2.771	55	2.820	63	2.869	68		
3 0 1	2.545	72	2.620	77	2.694	79		
0 1 1	2.467	100	2.536	100	2.605	100		

34-282 Ca_2CuO_3			34-283 Sr_2CuO_3	
$h\ k\ \ell$	d	I	d	I
3 1 0	2.771	55	2.870	65
3 0 1	2.545	80	2.694	85
0 1 1	2.467	100	2.604	100

FOM	77.20	81.23
Nobs	18	16
Nposs	27	24
$\Delta 2\theta$	0.009	0.008

Appendix B lists the simulated 2θ , d , $h\ k\ \ell$, and I values for the entire $\text{Ca}_{2-x}\text{Sr}_x\text{CuO}_3$ (for $x = 0$ to 2 in steps of 0.1) solid solution series. The (011) peak displays a $\Delta 2\theta$ greater than 0.2° as x changes by 0.2.

The PDF cards available for the end members of this solid solution series [Ca_2CuO_3 (34-282), Sr_2CuO_3 (34-283)] seem to agree well with the simulated patterns and have excellent FOMs, $F(18) = 77.20$ (0.009,27) and $F(16) = 81.23$ (0.008,24), respectively. Consequently, no change seems to be required. However, it is recommended that every other one of the solid solution patterns be incorporated into the PDF.

3.3 $(\text{Ca,Sr})_{14}\text{Cu}_{24}\text{O}_{41}$

The structure, composition, and limit of Ca solubility in $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ has been debated by a number of authors.^{3,4,6,7,26,27} According to Siegrist et al.,²⁷ $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ seems to display an incommensurate structure along the c -axis, but it becomes nearly commensurate at seven times the c -axis. McCarron et al.²⁶ report that $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ is

composed of two distinct subcells whose **a** and **b** parameters are equal but whose **c** parameters are 2.7Å for the CuO₂ subcell and 3.9Å for the Sr₂Cu₂O₃ subcell. These subcells become nearly commensurate at ten times the 2.7Å cell and seven times the 3.9Å cell.

The PDF contains two cards whose formulae are close to the same ratio of Sr:Cu:O and have cell parameters similar to the basic cell parameters described by Siegrist et al.²⁷ These cards are 39-250 (SrCu₂O₃) [ref. 28] and 39-489 (Sr_{1.75}Cu₃O_{5.13}) [ref. 29].

Table 9 displays the crystallographic data as described by Siegrist et al.²⁷ Table 10 displays the cell parameters as a function of Ca concentration according to McCarron et al.²⁶ Table 11 displays the three major XRD lines of the reference patterns and simulated patterns across the solid solution series up to Ca₇Sr₇Cu₂₄O₄₁. McCarron et al.²⁶ reports that as the Ca concentration approaches Ca₆Sr₈Cu₂₄O₄₁, a structure change occurs. For this study this lower limit of Ca solubility was ignored.

Table 9. (Ca,Sr)₁₄Cu₂₄O₄₁ crystallographic parameters²⁷

Struct.	S.G.	Atom	Occ. 0<x<1	x	y	z
Ortho	Cccm (66)	Sr	8-8x	0.2482	0.1168	0.0
		Sr2	16-16x	0.2514	0.1166	0.14256
		Sr3	16-16x	0.2489	0.1166	0.28566
		Sr4	16-16x	0.2504	0.1166	0.42879
		Cu1	16	0.0833	0.2492	0.07139
		Cu2	16	0.0831	0.2549	0.21447
		Cu3	16	0.0829	0.2452	0.35747
		Cu4	8	0.0835	0.2544	0.50000
		Cu5	4	0.0000	0.0000	0.00000
		Cu6	8	0.0000	0.0000	0.10100
		Cu7	8	0.0000	0.0000	0.19870
		Cu8	8	0.0000	0.5000	0.04760
		Cu9	8	0.0000	0.5000	0.14900
		Cu10	4	0.0000	0.5000	0.25000
		O1	8	0.0864	0.2662	0.00000
		O2	16	0.0839	0.2404	0.14330

Table 9. (continued)

Struct.	S.G.	Atom	Occ. 0<x<1	x	y	z
		O3	16	0.0834	0.2458	0.28660
		O4	16	0.0851	0.2425	0.42880
		O5	8	0.2500	0.2500	0.07060
		O6	8	0.2500	0.2500	0.21470
		O7	8	0.2500	0.2500	0.35780
		O8	4	0.2500	0.2500	0.50000
		O9	16	0.1181	0.0176	0.05350
		O10	8	0.1184	0.0000	0.25000
		O11	16	0.1211	0.0298	0.35160
		O12	16	0.1196	0.4957	0.10370
		O13	16	0.1203	0.4790	0.19650
		O14	8	0.1208	0.4721	0.50000
		Ca1	8x	0.2482	0.1168	0.00000
		Ca2	16x	0.2514	0.1166	0.14256
		Ca3	16x	0.0000	0.2489	0.11660
		Ca4	16x	0.0000	0.2504	0.11660

Table 10. (Ca,Sr)₁₄Cu₂₄O₄₁ unit cell parameters,²⁶ D_x, and I/I_c

Phase Ca:Sr:Cu	a	b	c	D _x	I/I _c
0:14:24	11.469	13.400	27.650	5.226	3.070
1:13:24	11.448	13.354	27.659	5.282	2.989
2:12:24	11.438	13.313	27.659	5.223	2.901
3:11:24	11.420	13.257	27.610	5.187	2.820
4:10:24	11.394	13.150	27.510	5.184	2.732
5:9:24	11.380	13.060	27.450	5.160	2.644
6:8:24	11.375	13.010	27.440	5.100	2.561
7:7:24	11.371	12.986	27.392	5.049	2.489

Table 11. Three major lines of simulated $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_3\text{Sr}_{11}\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_5\text{Sr}_9\text{Cu}_{24}\text{O}_{41}$, $\text{Ca}_7\text{Sr}_7\text{Cu}_{24}\text{O}_{41}$, observed $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ (ref. 4) and PDF cards 39-489 ($\text{Sr}_{1.75}\text{Cu}_3\text{O}_{5.13}$) and 39-250 (SrCu_2O_3)

	$\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$		$\text{Ca}_3\text{Sr}_{11}\text{Cu}_{24}\text{O}_{41}$		$\text{Ca}_5\text{Sr}_9\text{Cu}_{24}\text{O}_{41}$		$\text{Ca}_7\text{Sr}_7\text{Cu}_{24}\text{O}_{41}$	
$h\ k\ \ell$	d	I	d	I	d	I	d	I
2 4 0	2.893	100	2.866	100	2.832	93	2.813	100
1 3 7	2.865	85	2.850	87	2.823	100	2.813	100
3 1 7	2.691	56	2.682	54	2.669	46	2.665	41

	39-250 SrCu_2O_3		Roth et al. ⁴ $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$		39-489 $\text{Sr}_{1.75}\text{Cu}_3\text{O}_{5.13}$	
$h\ k\ \ell$	d	I	d	I	d	I
2 4 0	2.898	100	2.8879	100	2.894	100
1 3 1	2.866	80	2.8608	66	2.867	80
3 1 1	2.687	65	2.6853	52	2.692	42

FOM	41.36	47.65	61.79
Nobs	29	30	30
Nposs	56	32	32
$\Delta 2\theta$	0.013	0.017	0.013

Appendix C lists the complete 2θ , d , $h\ k\ \ell$, and I values for the entire $(\text{Ca},\text{Sr})_{14}\text{Cu}_{24}\text{O}_{41}$ solid solution series from $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ up to $\text{Ca}_7\text{Sr}_7\text{Cu}_{24}\text{O}_{41}$. The (240) peak displays a $\Delta 2\theta$ greater than 0.2° as the x in $\text{Ca}_x\text{Sr}_{14-x}\text{Cu}_{24}\text{O}_{41}$ changes by 2. At $x = 5$ the (240) peak overlaps the strong (137) and the apparent peak shifts significantly. It is therefore recommended that the patterns for $x = 0, 2, 4, 5$, and 7 be incorporated into the PDF.

PDF card 39-489 ($\text{Sr}_{1.75}\text{Cu}_3\text{O}_{5.13}$) agrees fairly well with the simulated pattern for $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ in terms of d and I . However, 39-489 reports a space group of $Fmmm$, whereas the simulated pattern (crystal structure taken from Siegrist et al.²⁷) and the observed pattern reported by Roth et al.⁴ use a space group of $Cccm$.

PDF card 39-250 with formula $\text{SrCu}_2\text{SrO}_3$ is likely $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$, since SrCu_2O_3 does not occur in the phase diagram. This pattern seems to contain a number of extraneous peaks when compared to the simulated or the pattern observed by Roth et al.⁴

Furthermore, this pattern, although it has a "*" rating, does not show a space group or a calculated density.

The pattern observed by Roth et al.⁴ for $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$ corresponds closely to the simulated pattern and has an adequate FOM [$F(30) = 47.65 (0.017, 37)$]. We highly recommend that these simulated patterns and the pattern observed by Roth et al.⁴ replace PDF cards 39-489 and 39-250.

3.4 (Ca,Sr)CuO₂

The (Ca,Sr)CuO₂ solid solution series has been reported by a number of authors.^{2-4,6,7,16,19,21,23,30-32} Most authors agree that the Ca solubility hits a limit around $\text{Ca}_{0.75}\text{Sr}_{0.25}\text{CuO}_2$. If more Ca is added, a structure change from orthorhombic to tetragonal occurs producing tetragonal $\text{Ca}_{0.86}\text{Sr}_{0.14}\text{CuO}_2$ (refs. 2,6). At higher Ca concentrations, CaCuO₂ forms with a different structure. CaCuO₂ has been reported by Roth et al.² and is stable up to 740°C. Orthorhombic SrCuO₂ is stable up to 955°C (ref. 3).

Table 12 presents the crystallographic data for the (Ca,Sr)CuO₂ solid solution series and the tetragonal phase. Table 13 displays the change in lattice parameters as a function of Ca concentration for the orthorhombic and tetragonal phases. Table 14 displays the PDF and simulated XRD data for the orthorhombic solid solution series. Table 15 displays the simulated and observed XRD data for the tetragonal phase.

Table 12. (Ca,Sr)₂CuO₂ crystallographic parameters^{23,30}

Struct.	S.G.	Atom	Occ. 0 < x < 1	x	y	z
Ortho	Cmcm (63)	Sr	4-4x	0.0000	0.3340	0.2500
		Ca	4x	0.0000	0.3340	0.2500
		Cu	4	0.0000	0.0640	0.2500
		O1	4	0.0000	0.9450	0.2500
		O2	4	0.0000	0.1780	0.2500
Tetragonal (0.14:0.86)	P4/mmm (123)	Sr	1-1x	0.5000	0.5000	0.5000
		Ca	1x	0.5000	0.5000	0.5000
		Cu	1	0.0000	0.0000	0.0000
		O	2	0.0000	0.5000	0.0000

Table 13. (Ca,Sr)CuO₂ and Ca_{0.86}Sr_{0.14}CuO₂ unit cell parameters,^{2,23,31,32} D_x, and I/I_c

Phase Sr:Ca	a	b	c	D _x	I/I _c
1:0	3.5730	16.33130	3.91360	5.326	3.813
0.9:0.1	3.5492	16.29184	3.90548	5.246	3.639
0.8:0.2	3.5254	16.25238	3.89736	5.164	3.460
0.7:0.3	3.5016	16.21292	3.88924	5.080	2.294
0.6:0.4	3.4778	16.17346	3.88112	4.993	3.123
0.5:0.5	3.4540	16.13400	3.87300	4.904	2.953
0.4:0.6	3.4302	16.09454	3.86488	4.813	2.785
0.3:0.7	3.4064	16.05508	3.85676	4.719	2.618
0.25:0.75	3.3945	16.03535	3.85270	4.671	2.785
0.14:0.86	3.8611	3.8611	3.1995	4.952	5.455
1:0	10.588	2.8122	6.3245	--	--

Table 14. Three main peaks of simulated SrCuO₂, Ca_{0.3}Sr_{0.7}CuO₂, Ca_{0.25}Sr_{0.75}CuO₂, and PDF cards: 39-1492(SrCuO₂) and 38-1179 (SrCuO₂)

	SrCuO ₂		Ca _{0.3} Sr _{0.7} O ₂		Ca _{0.75} Sr _{0.25} O ₂	
h k l	d	I	d	I	d	I
1 3 0	2.987	65	2.939	62	2.865	55
0 4 1	2.825	56	2.806	57	2.778	60
1 1 1	2.605	100	2.569	100	2.515	100

	39-1492 SrCuO ₂		38-1179 SrCuO ₂	
h k l	d	I	d	I
1 3 0	2.989	73	2.986	75
0 4 1	2.826	71	2.825	75
1 1 1	2.606	100	2.603	100

FOM	75.92	66.98
Nobs	30	30
Nposs	35	39
Δ2θ	0.010	0.011

Table 15. Four main peaks of tetragonal $\text{Ca}_{0.86}\text{Sr}_{0.14}\text{CuO}_2$

$h\ k\ \ell$	Simulated		Roth et al. ²	
	d	I	d	I
1 1 0	2.7300	32	2.7372	14
1 0 1	2.4640	100	2.4768	100
2 0 0	1.9305	34	1.9345	30
2 1 1	1.5196	33	1.5254	42
FOM		50.76		
Nobs		23		
Nposs		23		
$\Delta 2\theta$		0.013		

Appendix D lists the complete 2θ , d, $h\ k\ \ell$, and I values for the entire (Ca,Sr)CuO₂ solid solution series up to $\text{Ca}_{0.75}\text{Sr}_{0.25}\text{CuO}_2$. Appendix E lists the complete XRD data for the tetragonal phase ($\text{Ca}_{0.86}\text{Sr}_{0.14}\text{CuO}_2$). The (111) peak in the orthorhombic phase displays a $\Delta 2\theta$ greater than 0.16° as the x in $\text{Ca}_x\text{Sr}_{1-x}\text{CuO}_2$ changes by 0.1 for the orthorhombic phase. It is therefore recommended that all of the orthorhombic patterns and the one tetragonal simulated pattern be incorporated into the PDF.

PDF cards 39-1492 (ref. 31) and 38-1179 (ref. 32) [both SrCuO_2] agree reasonably well within the simulated patterns and have good FOMs [$F(30) = 75.95$ (0.010,39) and $F(30) = 66.98$ (0.012,39), respectively]. However, since they are both dealing with the same phase, it is recommended that 38-1179 be deleted as it has more discrepancies with the intensities of the simulated pattern.

Since no PDF card is available for the tetragonal phase, it is recommended that the pattern observed by Roth et al.² [$F(23) = 50.76$ (0.013, 23)] and the simulated pattern be incorporated into the PDF.

At the high-Ca end, the phase (CaCuO_2) has been reported by Roth et al.² The four main peaks of the pattern for CaCuO_2 observed by Roth et al.² are presented in Table 16. Available crystallographic data for this phase are limited, so a simulated pattern is not yet possible. However, a least-squares study of the pattern observed by Roth et al.² indicates that it is relatively reliable [$F(15) = 39.63$ (0.017,22)] and should be placed in the PDF until more data can be obtained.

Table 16. Four main peaks for observed
CaCuO₂ (ref. 2)

h k l	d	I
0 0 2	3.1620	26
2 0 2	2.7153	100
3 1 1	2.0751	42
5 1 1	1.6322	22
FOM	39.63	
Nobs	15	
Nposs	22	
$\Delta 2\theta$	0.0172	

3.5 (Ca,Sr)Cu₂O₃

The existence of CaCu₂O₃ has been reported by many authors.^{2,6,20,33-35} The atomic positions and crystal structure of four different models as compiled by Teske et al.³⁴ and Hoppe³⁵ are present in Table 17. Table 17 also contains the I/I_c and D_x values calculated in our studies. According to Roth et al.,² CaCu₂O₃ is only stable from 920 to 1020°C.

Table 17. (Ca,Sr)Cu₂O₃ crystallographic parameters³⁵
and I/I_c (for all four models: a = 9.942; b = 4.0786;
c = 3.459; D_x = 5.094)

Model/ structure	S.G.	Atom	Occ. 0 < x < 1	x	y	z	I/I _c
1/Ortho	Pmma (59)	Ca	2-2x	0.25	0.25	0.3633	1.686
		Cu	4	0.084	0.75	0.84	
		O(1)	2	0.25	0.75	0.595	
		O(2)	4	0.079	0.25	0.871	
		Sr	2x	0.25	0.25	0.3633	
2/Ortho	Pmma (59)	Ca	2-2x	0.25	0.25	0.3633	1.742
		Cu	4	0.081	0.75	0.847	
		O(1)	2	0.25	0.75	0.595	
		O(2)	4	0.087	0.25	0.826	
		Sr	2x	0.25	0.25	0.3633	

Table 17. (continued)

Model/ structure	S.G.	Atom	Occ. $0 < x < 1$	x	y	z	I/I _c
3/Ortho	Pmma (59)	Ca	2-2x	0.25	0.25	0.3633	2.302
		Cu	4	0.084	0.75	0.84	
		O(1)	2	0.25	0.75	0.115	
		O(2)	4	0.088	0.25	0.833	
		Sr	2x	0.25	0.25	0.3633	
4/Ortho	Pmma (59)	Ca	2-2x	0.25	0.25	0.3633	2.244
		Cu	4	0.084	0.75	0.84	
		O(1)	2	0.250	0.75	0.115	
		O(2)	4	0.082	0.25	0.853	
		Sr	2x	0.25	0.25	0.3633	

More data are necessary to determine the limit of solubility of Sr in this phase. Table 18 presents the simulated patterns of the four different models of CaCu_2O_3 (ref. 33). To determine which model is most accurate, more experimental data are needed.

Table 18. Three strongest lines for the four different structure models of CaCu_2O_3 presented by Hoppe³⁵ and PDF card 34-284 (CaCu_2O_3)

h k l	d	Model: 1 2 3 4				34-284	
		I	I	I	I	d	I
0 1 1	2.638	91	75	40	44	2.639	100
3 1 0	2.572	74	72	55	56	2.571	60
3 0 1	2.393	100	100	100	100	2.392	70
FOM						65.43	
Nobs						20	
Npos						32	
$\Delta 2\theta$						0.010	

Appendix F lists the complete 2θ , d, h k l, and I values for all four models of CaCu_2O_3 . The intensities change significantly.

The simulated patterns for CaCu_2O_3 seem to differ significantly from the PDF card 34-284 [$F(20) = 65.43$ (0.0010,32)]. Experimental studies on this particular phase and the effects of Sr substitution are currently under way.

3.6 $(\text{Ca,Sr})\text{Cu}_2\text{O}_2$

The effects of Ca solid solution on SrCu_2O_2 have not been studied, and as a result, powder pattern simulations cannot be calculated. However, Teske et al.³⁶ and Klockow et al.³⁷ have extensively studied the known end member of SrCu_2O_2 , which can only be produced in an O_2 -deficient atmosphere. Since such conditions are common in the formation of BSCCO superconductors, this phase should be more closely studied. Tables 19, 20, and 21 display the crystallographic data, lattice parameters, the three strongest lines of PDF card 38-1178 (SrCu_2O_2) [ref. 37] and a simulated pattern for this phase, respectively.

Table 19. SrCu_2O_2 crystallographic parameters³⁶

Structure	S.G.	Atom	Occ.	x	y	z
Tet.	141	Sr	4	0.0	0.0	0.0
		Cu	8	0.0	0.25	0.625
		O	8	0.0	0.0	0.5

Table 20. SrCu_2O_2 unit cell parameters,³⁷ D_x , and I/I_c

Phase	a	b	c	D_x	I/I_c
SrCu_2O_2	5.469	5.469	9.826	5.575	4.384

Table 21. Three main peaks of SrCu_2O_2 and PDF card 38-1178 (SrCu_2O_2)

h k ℓ	SrCu_2O_2		38-1178	
	d	I	d	I
1 1 2	3.039	100	3.041	20
1 0 3	2.810	51	2.811	90
2 1 1	2.373	66	2.372	100
FOM			37.01	
Nobs			25	
Npos			49	
$\Delta 2\theta$			0.014	

Appendix G lists the complete 2θ , d, h k ℓ , and I values for SrCu_2O_2 . Though the 2θ and h k ℓ values for this simulated pattern and PDF card 38-1178 [$F(25) = 37.01 (0.014, 49)$] are in reasonable agreement, the intensities differ significantly. Consequently, more data are needed to determine which pattern is correct. Until the ambiguity is resolved, both patterns should be in the PDF.

4. CONCLUSIONS

The XRD patterns of phases found in the CaO-SrO-CuO ternary system have been reviewed and simulated to produce recommended powder patterns for these phases. In order to obtain a complete understanding of the BSCCO system, a complete XRD study of the Ca-Sr-Cu-O phases must include further analysis of the $(\text{Ca}, \text{Sr})\text{Cu}_2\text{O}_3$, and the $(\text{Ca}, \text{Sr})\text{Cu}_2\text{O}_2$ systems. Without this analysis, phases formed in low-oxygen partial pressures or that are only present at high temperatures cannot be accurately identified.

5. ACKNOWLEDGMENTS

The assistance of the International Centre for Diffraction Data, O. B. Cavin of the High Temperature Materials Laboratory X-ray Diffraction User Center, the support of the Oak Ridge Science and Engineering Research Semester, and Oak Ridge Associated Universities are gratefully acknowledged.

6. REFERENCES

1. H. Maeda et al., "A New High-Tc Oxide Superconductor without a Rare Earth Element," *Jpn. J. Appl. Phys.* **27**, L209 (1988).
2. R. Roth et al., "Phase Equilibria of the System SrO-CaO-CuO," *J. Am. Ceram. Soc.* **72**(8), 1545 (1989).
3. R. Roth et al., "Phase Equilibria and Crystal Chemistry in the Quaternary System Ba-Sr-Y-Cu-O in Air," *J. Am. Ceram. Soc.* **72**(3), 395 (1989).
4. R. Roth et al., "Phase Equilibria and Crystal Chemistry in Portions of the System SrO-CaO-Bi₂O₃-CuO, Part II - The System SrO-Bi₂O₃-CuO," *J. Res. Natl. Inst. Stand. Technol.* **95**, 291 (1990).
5. P. Majewski et al., "Phase Equilibrium Diagrams of Bi₂O₃-SrO-CaO-CuO," to be published in *Adv. Mater.*
6. K. Schultze et al., "Phase Equilibrium in the System Bi₂O₃-SrO-CaO-CuO - A Tool for Processing the High-Tc Superconducting Bismuth Compounds," to be published in *Zeitschrift fur Metallkunde*.
7. M. Vallino et al., "Subsolidus Phase Relations in the SrO-CaO-CuO-O and SrO-Y₂O₃-CaO-O Systems," *Mater. Chem. Phys.* **22**, 523 (1989).
8. C. Lee et al., "Equilibrium Phase Relations in the Bi-Ca-Sr-Cu-O system at 850 & 900°C," *J. Mater. Res.* **5**(7), 1403 (1990).
9. D. Matheis and R. Snyder, "Crystal Structure and Powder Diffraction Patterns of the Bismuth and Thallium Ruddlesdon Popper Copper Oxide Superconductors," *Powder Diff.* **5**(1), 8 (1990).
10. D. Smith, and K. Smith, "MICRO-POWD: A Program for Calculating X-ray Powder Diffraction Patterns on a P.C.," Materials Data, Inc., Copyright 1987.
11. H. Evens, Jr, D. Appleman, and D. Handwerder, Report PB216188, U.S. Dept. of Commerce, National Technical Information Center, Springfield, Va., 1963.
12. H. McMurdie et al., "Standard X-ray Diffraction Powder Patterns from the JCPDS Research Associateship," *Powder Diff.* **1**(3), 265 (1986).
13. H. Swanson, N. Gilfrich, and G. Ugrinic, "Standard X-ray Diffraction Powder Patterns," *Natl. Bur. Stand. (U.S.) Circ.* **529** **5**, 69 (1955).
14. Obst and Munchberg, *Tonid. Zeitg.* **6**, 92 (1968).
15. H. Swanson et al., "Standard X-ray Diffraction Powder Patterns," *Natl. Bur. Stand. Monog.* **25**(5), 43 (1967).

16. W. Carrilo-Calrera, and W. Göpel, "Influence of High-Temperature Annealing on the $(\text{Bi,Pb})_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$ Phase and Determination of its Crystal Structure by X-ray Powder Diffractometry," *Phys. C* **161**, 373 (1989).
17. H. Hoshizaki et al., "Direct Observations of Melting and Solidification of Bi-Pb-Sr-Ca-Cu-O Compounds," *Jpn. J. App. Phys.* **29**, 1444 (1990).
18. H. Susakura et al., "Single High-Tc Phase Regions of the Bi-Pb-Sr-Ca-Cu-O System," *Jpn. J. App. Phys.* **28(7)**, L1163 (1989).
19. Y. Oka et al., "Crystalline Phases formed in the Partially Melted States of Bi-Ca-Sr-Cu-O," *Jpn. J. Appl. Phys.* **28(5)**, L801 (1989).
20. P. Trembley and M. Gasgnier, "Energy Dispersive X-ray (EDX) Chemical Analysis of High-Tx Superconducting Phases in the Bi-Ca-Sr-Cu-O System," *J. Microsc. Spectrosc. Electron.* **14**, 75 (1989).
21. H. Muller-Buschbaum, "Oxometallates w/Planar Coordination," *Angew. Chem. Int. Ed. Eng.* **16**, 674 (1987).
22. V.C. L. Teske and H. Muler-Buschbaum, "Zur Kennitnis von Sr_2CuO_3 ," *Zeit. Anorg. Allge. Chemie.* **371**, 325 (1969).
23. V.C. L. Teske and H. Muler-Buschbaum, "Zur Kennitnis von Ca_2CuO_3 und SrCuO_2 ," *Zeit. Anorg. Allge. Chemie.* **379**, 234 (1970).
24. Breuer and Eysel, *JCPDS Grant-in-Aid Report*, 1982.
25. Breuer and Eysel, *JCPDS Grant-in-Aid Report*, 1981.
26. E. McCarron III et al., "The Incommensurate Structure of $(\text{Sr}_{14-x}\text{Ca}_x)\text{Cu}_{24}\text{O}_{41}$ ($0 < x \sim 8$) A Superconductor By-product," *Mater. Res. Bull.* **23**, 1355 (1988).
27. T. Siegrist et al., "A New Layered Cuprate Structure Type $(\text{A}_{1-x}\text{A}'_x)_{14}\text{Cu}_{24}\text{O}_{41}$," *Mater. Res. Bull.* **23**, 1429 (1988).
28. Klockow and Eysel, *JCPDS Grant-in-Aid Report*, 1988.
29. W. Wong-Ng et al., *JCPDS Grant-in-Aid Report* 1988.
30. T. Siegrist et al., "The Parent Structure of the Layered High-Temperature Superconductor," *Nature* **334**, 21 (1988).
31. W. Wong-Ng et al., *JCPDS Grant-in-Aid Report*, 1987.
32. Popp and Eysel, *JCPDS Grant-in-Aid Report*, 1987.
33. Breuer and Eysel, *JCPDS Grant-in-Aid Report*, 1982.
34. V.C. L. Teske and H. Muller-Buschbaum, "Zur Kennitnis von CaCu_2O_3 ," *Zeit. Anorg. Allge. Chemie.* **370**, 134 (1969).
35. V. R. Hoppe, "Zur Gitterenergie von CaCu_2O_3 ," *Zeit. Anorg. Allge. Chemie.* **370**, 144 (1969).

36. V.C. L. Teske and H. Muller-Buschbaum, "Zur Kenntnis von SrCu_2O_2 ," *Zeit. Anorg. Allge. Chemie.* **379**, 113 (1970).
37. Klockow and Eysel, *JCPDS Grant-in-Aid Report*, 1987.

APPENDIX A: (Ca,Sr)O

Table A.1. Simulated X-ray powder pattern for
CaO

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
32.20	32.20	2.777	1	1	1	40	41	33
37.36	37.36	2.405	2	0	0	100	100	100
53.86	53.86	1.7008	2	2	0	51	47	84
64.16	64.16	1.4504	3	1	1	17	15	36
67.38	67.38	1.3887	2	2	2	14	12	31
79.66	79.66	1.2026	4	0	0	5	5	16
88.53	88.52	1.1036	3	3	1	7	5	23
91.47	91.46	1.0757	4	2	0	14	11	50
103.34	103.34	.9820	4	2	2	11	9	47
112.62	112.62	.9258	5	1	1	5	5	25
112.62		.9258	3	3	3	2		8
129.86	129.86	.8504	4	4	0	5	3	31
142.64	142.64	.8131	5	3	1	15	7	97
147.79	147.78	.8018	4	4	2	15	7	101
147.79		.8018	6	0	0	4		25

Table A.2. Simulated X-ray powder pattern for
Ca_{0.9}Sr_{0.1}O

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
31.97	31.98	2.798	1	1	1	47	48	39
37.08	37.08	2.423	2	0	0	100	100	100
53.44	53.44	1.7132	2	2	0	52	48	87
63.64	63.64	1.4610	3	1	1	20	17	42
66.83	66.84	1.3988	2	2	2	14	12	33
78.97	78.98	1.2114	4	0	0	6	5	17
87.73	87.72	1.1116	3	3	1	8	6	27
90.62	90.62	1.0835	4	2	0	15	12	54
102.30	102.30	.9891	4	2	2	12	9	49
111.39	111.38	.9325	5	1	1	6	6	28
111.39		.9325	3	3	3	2		9
128.13	128.12	.8566	4	4	0	6	3	32
140.27	140.26	.8190	5	3	1	16	7	103
145.04	145.04	.8076	4	4	2	15	8	98
145.04		.8076	6	0	0	4		25

Table A.3. Simulated X-ray powder pattern for
 $\text{Ca}_{0.8}\text{Sr}_{0.2}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
31.73	31.74	2.818	1	1	1	53	55	44
36.80	36.80	2.440	2	0	0	100	100	100
53.03	53.04	1.7255	2	2	0	53	48	89
63.13	63.14	1.4715	3	1	1	22	20	48
66.29	66.28	1.4089	2	2	2	15	13	34
78.30	78.30	1.2201	4	0	0	6	5	18
86.94	86.94	1.1197	3	3	1	9	7	30
99.80	89.80	1.0913	4	2	0	16	13	57
101.29	101.28	.9962	4	2	2	12	9	52
110.19	110.20	.9392	5	1	1	6	6	31
110.19		.9392	3	3	3	2		10
126.46	126.46	.8628	4	4	0	6	3	33
138.06	138.06	.8249	5	3	1	16	8	107
142.52	142.52	.8134	4	4	2	14	8	96
142.52		.8134	6	0	0	4		24

Table A.4. Simulated X-ray powder pattern for
 $\text{Ca}_{0.7}\text{Sr}_{0.3}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
31.50	31.50	2.838	1	1	1	59	61	49
36.53	36.54	2.458	2	0	0	100	100	100
52.62	52.62	1.7379	2	2	0	55	50	92
62.63	62.64	1.4821	3	1	1	25	22	54
65.76	65.76	1.4190	2	2	2	15	13	36
77.64	77.64	1.2289	4	0	0	6	5	19
86.17	86.18	1.1277	3	3	1	10	8	33
88.99	88.98	1.0991	4	2	0	16	13	60
100.30	100.30	1.0034	4	2	2	12	10	54
109.04	109.04	.9460	5	1	1	7	7	33
109.04		.9460	3	3	3	2		11
124.87	124.88	.8689	4	4	0	6	4	33
135.98	135.98	.8309	5	3	1	17	8	110
140.19	140.20	.8192	4	4	2	14	8	94
140.19		.8192	6	0	0	3		24

Table A.5. Simulated X-ray powder pattern for
 $\text{Ca}_{0.6}\text{Sr}_{0.4}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
31.27	31.28	2.858	1	1	1	64	67	53
36.26	36.26	2.475	2	0	0	100	100	100
52.22	52.22	1.7502	2	2	0	56	51	94
62.14	62.14	1.4926	3	1	1	27	24	59
65.24	65.24	1.4290	2	2	2	16	14	37
76.99	76.98	1.2376	4	0	0	6	5	19
85.42	85.42	1.1357	3	3	1	10	9	37
88.20	88.20	1.1069	4	2	0	17	14	62
99.34	99.34	1.0105	4	2	2	13	10	56
107.91	107.90	.9527	5	1	1	7	7	36
107.91		.9527	3	3	3	2		12
123.34	123.34	.8751	4	4	0	6	4	34
134.02	134.02	.8368	5	3	1	17	9	113
138.02	138.02	.8251	4	4	2	13	8	93
138.02		.8251	6	0	0	3		23

Table A.6. Simulated X-ray powder pattern for
 $\text{Ca}_{0.5}\text{Sr}_{0.5}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
31.05	31.06	2.878	1	1	1	69	71	57
36.00	36.00	2.493	2	0	0	100	100	100
51.83	51.84	1.7626	2	2	0	56	51	95
61.66	61.66	1.5031	3	1	1	29	26	64
64.72	64.72	1.4391	2	2	2	16	14	38
76.35	76.34	1.2463	4	0	0	7	5	20
84.68	84.68	1.1437	3	3	1	11	9	39
87.42	87.42	1.1147	4	2	0	17	14	65
98.39	98.40	1.0176	4	2	2	13	10	58
106.81	106.82	.9594	5	1	1	8	8	38
106.81		.9594	3	3	3	3		13
121.87	121.86	.8813	4	4	0	6	4	34
132.16	132.16	.8427	5	3	1	17	9	115
135.97	135.98	.8309	4	4	2	13	8	91
135.97		.8309	6	0	0	3		23

Table A.7. Simulated X-ray powder pattern for $\text{Ca}_{0.4}\text{Sr}_{0.6}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
30.82	30.84	2.898	1	1	1	74	76	61
35.74	35.74	2.510	2	0	0	100	100	100
51.44	51.44	1.7749	2	2	0	57	53	97
61.18	61.18	1.5137	3	1	1	31	28	68
64.22	64.22	1.4492	2	2	2	17	15	39
75.72	75.72	1.2551	4	0	0	7	6	21
83.95	83.96	1.1517	3	3	1	12	10	42
86.66	86.66	1.1226	4	2	0	18	15	67
97.47	97.48	1.0248	4	2	2	13	11	60
105.74	105.74	.9661	5	1	1	8	8	40
105.74		.9661	3	3	3	3		13
120.45	120.44	.8875	4	4	0	6	4	34
130.39	130.40	.8486	5	3	1	17	10	116
134.04	134.04	.8367	4	4	2	13	8	89
134.04		.8367	6	0	0	3		22

Table A.8. Simulated X-ray powder pattern for $\text{Ca}_{0.3}\text{Sr}_{0.7}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
30.61	30.62	2.919	1	1	1	78	81	64
35.49	35.50	2.528	2	0	0	100	100	100
51.06	51.06	1.7873	2	2	0	58	54	99
60.71	60.72	1.5242	3	1	1	33	29	73
63.72	63.72	1.4593	2	2	2	17	15	40
75.11	75.10	1.2638	4	0	0	7	6	21
83.24	83.24	1.1597	3	3	1	12	10	45
85.92	85.92	1.1304	4	2	0	18	15	69
96.58	96.58	1.0319	4	2	2	14	11	61
104.70	104.70	.9729	5	1	1	8	8	42
104.70		.9729	3	3	3	3		14
119.08	119.08	.8936	4	4	0	6	4	35
128.71	128.70	.8545	5	3	1	18	10	117
132.20	132.20	.8425	6	0	0	3	9	22
132.20		.8425	4	4	2	13		88

Table A.9. Simulated X-ray powder pattern for
 $\text{Ca}_{0.2}\text{Sr}_{0.8}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
30.39	30.40	2.939	1	1	1	82	85	67
35.24	35.24	2.545	2	0	0	100	100	100
50.69	50.68	1.7996	2	2	0	59	53	100
60.25	60.26	1.5347	3	1	1	35	30	77
63.23	63.24	1.4694	2	2	2	17	15	41
74.51	74.50	1.2725	4	0	0	7	6	22
82.55	82.54	1.1678	3	3	1	13	11	47
85.18	85.18	1.1382	4	2	0	19	15	71
95.70	95.70	1.0390	4	2	2	14	11	63
103.69	103.70	.9796	5	1	1	9	9	43
103.69		.9796	3	3	3	3		14
117.76	117.76	.8998	4	4	0	6	4	35
127.09	127.10	.8604	5	3	1	18	10	118
130.46	130.46	.8484	6	0	0	3	9	22
130.46		.8484	4	4	2	12		86

Table A.10. Simulated X-ray powder pattern for
 $\text{Ca}_{0.1}\text{Sr}_{0.9}\text{O}$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
30.18	30.18	2.959	1	1	1	86	89	70
34.99	35.00	2.563	2	0	0	100	100	100
50.32	50.32	1.8120	2	2	0	59	55	101
59.80	59.80	1.5453	3	1	1	36	32	81
62.75	62.76	1.4795	2	2	2	18	15	42
73.91	73.92	1.2813	4	0	0	7	6	23
81.86	81.86	1.1758	3	3	1	14	11	50
84.47	84.46	1.1460	4	2	0	19	15	72
94.84	94.84	1.0461	4	2	2	14	11	64
102.70	102.70	.9863	5	1	1	9	9	45
102.70		.9863	3	3	3	3		15
116.47	116.48	.9060	4	4	0	6	4	35
125.54	125.54	.8663	5	3	1	18	11	119
128.79	128.80	.8542	6	0	0	3	9	21
128.79		.8542	4	4	2	12		85

Table A.11. Simulated X-ray powder pattern for
SrO

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
29.97	29.98	2.979	1	1	1	89	93	73
34.74	34.74	2.580	2	0	0	100	100	100
49.95	49.96	1.8243	2	2	0	60	55	102
59.35	59.36	1.5558	3	1	1	38	34	84
62.28	62.28	1.4896	2	2	2	18	16	43
73.33	73.34	1.2900	4	0	0	7	6	23
81.19	81.20	1.1838	3	3	1	14	12	52
83.77	83.76	1.1538	4	2	0	19	16	74
94.00	94.00	1.0533	4	2	2	14	12	65
101.74	101.74	.9930	5	1	1	9	9	46
101.74		.9930	3	3	3	3		15
115.23	115.24	.9122	4	4	0	6	4	35
124.05	124.06	.8722	5	3	1	18	11	119
127.20	127.20	.8600	6	0	0	3	9	21
127.20		.8600	4	4	2	12		84

APPENDIX B: $(\text{Ca,Sr})_2\text{CuO}_3$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.47	14.48	6.117	2	0	0	25	31	10
24.65	24.66	3.609	1	1	0	2	2	1
28.33	28.34	3.148	1	0	1	18	19	13
29.17	29.18	3.059	4	0	0	1	1	1
32.28	32.28	2.771	3	1	0	45	46	39
35.24	35.24	2.545	3	0	1	67	67	64
36.39	36.40	2.467	0	1	1	100	100	100
39.35	39.36	2.288	2	1	1	0	0	0
44.06	44.06	2.054	5	1	0	7	7	8
44.39	44.40	2.039	6	0	0	30	29	38
46.38	46.38	1.9563	5	0	1	12	12	17
47.30	47.30	1.9200	4	1	1	5	5	6
48.15	48.14	1.8885	0	2	0	27	24	38
50.54	50.54	1.8044	2	2	0	2	2	3
56.45	56.46	1.6287	0	0	2	14	13	26
56.81	56.80	1.6194	1	2	1	2	3	4
58.11	58.70	1.5861	7	1	0	0	27	0
58.61		1.5738	2	0	2	1		2
58.70		1.5716	6	1	1	29		56
60.02	60.04	1.5400	7	0	1	0	0	0
60.49	60.50	1.5293	8	0	0	3	3	6
61.05	61.06	1.5166	3	2	1	22	19	44
62.52	62.52	1.4845	1	1	2	0	0	0
66.54	66.54	1.4041	3	1	2	11	10	25
67.56	67.56	1.3855	6	2	0	11	10	24

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
69.07	69.08	1.3587	5	2	1	5	4	12
72.69	72.70	1.2997	8	1	1	4	3	9
74.06	74.06	1.2790	9	1	0	2	2	6
74.26	74.28	1.2760	5	1	2	2	3	5
74.50	74.50	1.2725	6	0	2	8	7	20
75.76	75.76	1.2545	9	0	1	3	3	8
77.30	77.30	1.2333	0	2	2	8	7	23
78.05	78.04	1.2234	10	0	0	0	0	0
79.16	79.16	1.2090	2	2	2	1	1	2
79.64	79.64	1.2029	3	3	0	3	3	9
80.81	80.80	1.1884	8	2	0	2	2	6
81.99	81.98	1.1743	0	3	1	5	4	16
83.82	83.82	1.1532	2	3	1	0	0	0
85.36	85.36	1.1363	7	1	2	0	0	0
86.96	86.96	1.1195	5	3	0	1	1	2
87.41	87.42	1.1148	8	0	2	2	1	5
89.28	89.30	1.0963	4	3	1	0	1	1
89.31		1.0960	10	1	1	1		3

Table B.2. Simulated X-ray powder pattern for $\text{Ca}_{1.9}\text{Sr}_{0.1}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
14.44	14.46	6.128	2	0	0	30	37	12
24.61	24.62	3.615	1	1	0	1	1	1
28.23	28.24	3.159	1	0	1	15	16	11
29.12	29.12	3.064	4	0	0	2	2	1
32.22	32.22	2.776	3	1	0	46	47	40
35.13	35.14	2.553	3	0	1	67	67	64
36.29	36.30	2.474	0	1	1	100	100	100
39.24	39.24	2.294	2	1	1	1	1	1
43.98	43.98	2.057	5	1	0	6	7	8
44.31	44.30	2.043	6	0	0	27	26	35
46.25	46.26	1.9612	5	0	1	12	12	17
47.18	47.18	1.9247	4	1	1	7	7	10
48.06	48.06	1.8917	0	2	0	26	25	38
50.45	50.46	1.8075	2	2	0	2	2	3
56.23	56.24	1.6346	0	0	2	14	13	26
56.67	56.66	1.6229	1	2	1	2	2	4
57.18	57.18	1.6096	4	2	0	0	0	1
57.99	58.56	1.5890	7	1	0	0	25	0
58.38		1.5794	2	0	2	1		2
58.56		1.5751	6	1	1	27		51
60.37	60.38	1.5321	8	0	0	4	4	8
60.91	60.90	1.5198	3	2	1	22	19	44
62.29	62.28	1.4894	1	1	2	0	0	0
64.57	64.56	1.4422	4	0	2	0	0	0
66.31	66.30	1.4085	3	1	2	11	10	26

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
67.42	67.42	1.3880	6	2	0	10	9	24
68.91	68.92	1.3615	5	2	1	5	4	12
72.51	72.52	1.3025	8	1	1	5	4	14
73.91	74.02	1.2814	9	1	0	2	3	5
74.01		1.2798	5	1	2	2		6
74.25	74.24	1.2763	6	0	2	7	7	19
75.58	75.58	1.2571	9	0	1	3	2	7
77.04	77.04	1.2368	0	2	2	8	7	23
77.88	77.88	1.2257	10	0	0	0	0	0
78.89	78.90	1.2124	2	2	2	1	1	2
79.47	79.48	1.2050	3	3	0	3	3	9
80.63	80.64	1.1906	8	2	0	3	2	8
81.79	81.80	1.1766	0	3	1	5	4	16
83.62	83.62	1.1555	2	3	1	0	0	0
84.39	84.38	1.1469	4	2	2	0	0	1
85.07	85.08	1.1394	7	1	2	0	0	1
86.77	86.78	1.1214	5	3	0	1	1	2
87.12	87.12	1.1178	8	0	2	2	2	7
89.06	89.08	1.0984	4	3	1	0	1	2
89.08		1.0982	10	1	1	1		4

Table B.3. Simulated X-ray powder pattern for $\text{Ca}_{1.8}\text{Sr}_{0.2}\text{CuO}_3$

20	PEAK	d	h	k	l	(INT)	(PK)	(DS)
14.42	14.42	6.140	2	0	0	27	33	10
24.56	24.58	3.621	1	1	0	1	1	0
28.13	28.14	3.170	1	0	1	13	14	10
29.07	29.08	3.070	4	0	0	2	3	2
32.16	32.16	2.781	3	1	0	47	48	41
35.02	35.02	2.560	3	0	1	67	68	65
36.18	36.18	2.481	0	1	1	100	100	100
39.13	39.14	2.300	2	1	1	0	0	0
43.90	43.90	2.061	5	1	0	6	7	8
44.22	44.22	2.047	6	0	0	27	26	35
46.13	46.14	1.9661	5	0	1	12	11	16
47.06	47.06	1.9294	4	1	1	8	7	11
47.97	47.98	1.8949	0	2	0	26	24	38
50.36	50.36	1.8106	2	2	0	2	2	3
56.01	56.00	1.6406	0	0	2	14	13	26
56.54	56.54	1.6265	1	2	1	2	2	3
57.07	57.08	1.6125	4	2	0	0	1	1
57.88	57.90	1.5919	7	1	0	0	1	1
58.16	58.42	1.5850	2	0	2	1	24	2
58.41		1.5786	6	1	1	27		51
60.25	60.24	1.5349	8	0	0	4	4	8
60.76	60.76	1.5231	3	2	1	22	20	45
64.33	64.34	1.4469	4	0	2	0	0	1
66.07	66.08	1.4130	3	1	2	12	10	27
67.28	67.28	1.3904	6	2	0	10	9	24

20	PEAK	d	h	k	l	(INT)	(PK)	(DS)
68.75	68.74	1.3644	5	2	1	5	4	12
72.34	72.34	1.3052	8	1	1	5	4	14
73.75	73.76	1.2837	9	1	0	2	4	5
73.76		1.2836	5	1	2	2		6
73.99	73.98	1.2800	6	0	2	7	7	19
75.39	75.40	1.2598	9	0	1	3	2	7
76.79	76.78	1.2403	0	2	2	8	7	23
77.71	77.70	1.2279	10	0	0	0	0	1
78.63	78.64	1.2157	2	2	2	1	1	2
79.31	79.30	1.2071	3	3	0	3	3	10
80.46	80.46	1.1927	8	2	0	3	2	8
81.60	81.60	1.1789	0	3	1	5	4	17
83.42	83.42	1.1578	2	3	1	0	0	0
84.11	84.10	1.1500	4	2	2	0	0	1
84.79	84.80	1.1425	7	1	2	0	0	1
86.58	86.58	1.1234	5	3	0	1	1	2
86.83	86.84	1.1208	8	0	2	2	2	7
88.84	88.84	1.1006	4	3	1	1	1	2
88.85		1.1005	10	1	1	1		4

Table B.4. Simulated X-ray powder pattern for $\text{Ca}_{1.7}\text{Sr}_{0.3}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.39	14.40	6.151	2	0	0	24	29	9
24.52	24.52	3.628	1	1	0	0	0	0
28.03	28.04	3.181	1	0	1	11	12	8
29.01	29.02	3.075	4	0	0	3	3	2
32.10	32.12	2.786	3	1	0	48	48	42
34.92	34.92	2.566	3	0	1	68	68	65
36.08	36.08	2.488	0	1	1	100	100	100
39.03	39.04	2.306	2	1	1	0	0	0
43.81	43.82	2.065	5	1	0	6	7	8
44.14	44.14	2.050	6	0	0	26	25	34
46.01	46.02	1.9710	5	0	1	11	11	15
46.94	46.94	1.9341	4	1	1	8	8	12
47.88	47.88	1.8982	0	2	0	26	24	38
50.26	50.26	1.8138	2	2	0	2	1	3
55.79	55.78	1.6465	0	0	2	14	13	26
56.40	56.40	1.6300	1	2	1	1	1	2
56.96	56.96	1.6153	4	2	0	1	1	1
57.76	57.94	1.5948	7	1	0	0	2	1
57.93		1.5905	2	0	2	1		2
58.27	58.28	1.5821	6	1	1	27	24	52
60.13	60.12	1.5377	8	0	0	4	4	8
60.62	60.62	1.5263	3	2	1	22	20	46
64.10	64.10	1.4516	4	0	2	0	0	1
65.84	65.84	1.4174	3	1	2	12	10	28
67.15	67.16	1.3929	6	2	0	10	9	24

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
68.58	68.58	1.3672	5	2	1	5	4	11
72.16	72.16	1.3080	8	1	1	5	4	14
73.51	73.74	1.2873	5	1	2	2	7	5
73.59		1.2860	9	1	0	2		5
73.74		1.2838	6	0	2	7		19
75.21	75.20	1.2624	9	0	1	3	2	7
76.53	76.54	1.2438	0	2	2	8	7	24
77.54	77.54	1.2301	10	0	0	0	0	1
78.37	78.38	1.2191	2	2	2	1	0	2
79.14	79.14	1.2092	3	3	0	3	3	10
80.29	80.28	1.1948	8	2	0	3	2	8
81.40	81.40	1.1812	0	3	1	5	4	17
83.83	83.84	1.1531	4	2	2	0	0	1
84.51	84.52	1.1455	7	1	2	0	0	1
86.40	86.54	1.1253	5	3	0	1	2	2
86.54		1.1238	8	0	2	2		7
88.62	88.62	1.1027	10	1	1	1	2	5
88.62		1.1027	4	3	1	1		2

Table B.5. Simulated X-ray powder pattern for $\text{Ca}_{1.6}\text{Sr}_{0.4}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
14.36	14.38	6.162	2	0	0	21	26	8
27.93	27.94	3.192	1	0	1	9	10	7
28.96	28.96	3.081	4	0	0	3	4	3
32.05	32.06	2.791	3	1	0	49	50	43
34.81	34.82	2.575	3	0	1	68	69	66
35.97	35.98	2.495	0	1	1	100	100	100
38.92	38.92	2.312	2	1	1	0	0	0
43.73	43.74	2.068	5	1	0	6	6	7
44.05	44.06	2.054	6	0	0	26	25	34
45.89	45.90	1.9758	5	0	1	11	10	15
46.82	46.82	1.9387	4	1	1	9	9	13
47.80	47.80	1.9014	0	2	0	26	24	38
50.17	50.18	1.8169	2	2	0	1	1	2
55.57	55.58	1.6525	0	0	2	15	13	26
56.27	56.26	1.6336	1	2	1	1	1	2
56.86	56.86	1.6181	4	2	0	1	1	1
57.65	57.72	1.5977	7	1	0	1	2	1
57.71		1.5961	2	0	2	1		2
58.13	58.14	1.5856	6	1	1	27	23	52
60.00	60.00	1.5405	8	0	0	4	4	8
60.48	60.48	1.5296	3	2	1	23	20	47
63.87	63.88	1.4563	4	0	2	0	0	1
65.60	65.60	1.4219	3	1	2	12	11	28
67.02	67.02	1.3953	6	2	0	10	9	24
68.42	68.42	1.3701	5	2	1	4	4	11
71.99	71.98	1.3107	8	1	1	5	4	14
73.26	73.28	1.2910	5	1	2	2	2	5
73.44	73.48	1.2884	9	1	0	2	8	5
73.49		1.2875	6	0	2	7		19
75.02	75.02	1.2650	9	0	1	3	2	7
76.28	76.28	1.2473	0	2	2	8	7	24
77.37	77.38	1.2324	10	0	0	0	0	1
78.12	78.12	1.2225	2	2	2	0	0	1
78.98	78.98	1.2112	3	3	0	3	3	10
79.62	79.62	1.2032	7	2	1	0	0	0
80.11	80.12	1.1970	8	2	0	3	2	8
81.21	81.22	1.1835	0	3	1	5	4	17
83.56	83.56	1.1561	4	2	2	0	0	1
84.23	84.24	1.1486	7	1	2	0	0	1
86.21	86.24	1.1273	5	3	0	1	2	2
86.25		1.1268	8	0	2	2		7
88.40	88.40	1.1049	10	1	1	1	2	5
88.41		1.1048	4	3	1	1		3

Table B.6. Simulated X-ray powder pattern for $\text{Ca}_{1.5}\text{Sr}_{0.5}\text{CuO}_3$

[illegible]

Table B.8. Simulated X-ray powder pattern for $\text{Ca}_{1.3}\text{Sr}_{0.7}\text{CuO}_3$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.28	14.30	6.196	2	0	0	33	40	12
24.35	24.36	3.652	1	1	0	2	2	1
27.63	27.64	3.226	1	0	1	13	14	10
28.80	28.80	3.098	4	0	0	1	1	1
31.87	31.88	2.805	3	1	0	60	62	52
34.50	34.50	2.597	3	0	1	74	76	71
35.67	35.68	2.515	0	1	1	100	100	100
38.60	38.60	2.331	2	1	1	3	3	3
43.48	43.48	2.079	5	1	0	9	9	11
43.80	43.80	2.065	6	0	0	26	25	34
45.54	45.54	1.9904	5	0	1	13	13	18
46.47	46.46	1.9527	4	1	1	3	3	4
47.54	47.54	1.9111	0	2	0	25	24	37
49.90	49.90	1.8262	2	2	0	3	3	4
54.92	54.92	1.6704	0	0	2	15	14	27
55.87	55.88	1.6442	1	2	1	2	2	4
57.06	57.06	1.6128	2	0	2	2	2	3
57.71	57.72	1.5962	6	1	1	30	27	59
59.64	59.64	1.5489	8	0	0	5	5	9
60.05	60.06	1.5394	3	2	1	27	24	55
60.94	60.94	1.5190	1	1	2	1	1	1
64.92	64.92	1.4352	3	1	2	16	14	37
66.62	66.62	1.4027	6	2	0	11	10	27
67.94	67.94	1.3785	5	2	1	6	6	16
71.47	71.48	1.3189	8	1	1	7	6	19

20	PEAK	d	h'	k	l	I(INT)	I(PK)	I(DS)
72.53	72.54	1.3023	5	1	2	3	4	9
72.76	72.76	1.2987	6	0	2	8	9	22
72.98	72.96	1.2954	9	1	0	3	6	8
74.48	74.48	1.2730	9	0	1	4	3	10
74.86	74.70	1.2674	1	3	0	0	2	0
75.54	75.54	1.2577	0	2	2	9	8	27
77.36	77.36	1.2325	2	2	2	1	1	4
78.50	78.50	1.2175	3	3	0	4	4	14
79.60	79.60	1.2033	8	2	0	3	3	10
80.64	80.64	1.1904	0	3	1	6	5	20
82.43	82.44	1.1691	2	3	1	1	0	2
85.41	85.40	1.1358	8	0	2	3	2	9
85.66	85.66	1.1331	5	3	0	1	2	4
87.73	87.74	1.1116	10	1	1	0	0	1
87.77		1.1112	4	3	1	0		0
87.98	88.00	1.1091	1	0	3	0	0	1

Table B.9. Simulated X-ray powder pattern for $\text{Ca}_{1.2}\text{Sr}_{0.8}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
14.26	14.26	6.207	2	0	0	30	36	11
24.31	24.32	3.659	1	1	0	1	2	1
27.54	27.54	3.237	1	0	1	12	12	8
28.74	28.74	3.103	4	0	0	1	1	1
31.82	31.82	2.810	3	1	0	60	63	52
34.40	34.40	2.605	3	0	1	74	76	71
35.56	35.56	2.522	0	1	1	100	100	100
38.49	38.50	2.337	2	1	1	3	3	3
43.40	43.40	2.083	5	1	0	8	9	11
43.72	43.72	2.069	6	0	0	25	25	34
45.42	45.42	1.9953	5	0	1	13	12	18
46.35	46.36	1.9574	4	1	1	4	4	5
47.45	47.46	1.9144	0	2	0	25	24	38
49.81	49.80	1.8293	2	2	0	3	2	4
54.71	54.72	1.6763	0	0	2	15	14	28
55.74	55.74	1.6477	1	2	1	2	2	4
56.43	56.44	1.6293	4	2	0	0	0	0
56.85	56.84	1.6183	2	0	2	2	2	3
57.20	57.58	1.6092	7	1	0	0	27	0
57.57		1.5997	6	1	1	30		59
59.53	59.52	1.5517	8	0	0	4	5	9
59.91	59.92	1.5426	3	2	1	27	24	56
60.72	60.72	1.5240	1	1	2	0	1	1
64.70	64.70	1.4397	3	1	2	16	14	38
66.49	66.48	1.4051	6	2	0	11	10	27
67.78	67.78	1.3814	5	2	1	6	5	15
71.30	71.30	1.3217	8	1	1	7	6	19
72.29	72.30	1.3060	5	1	2	3	4	9
72.51	72.52	1.3025	6	0	2	8	8	22
72.82	72.72	1.2977	9	1	0	3	5	8
74.30	74.30	1.2756	9	0	1	4	3	10
74.71	74.50	1.2695	1	3	0	0	2	0
75.29	75.30	1.2612	0	2	2	9	8	27
77.11	77.12	1.2359	2	2	2	1	1	4
78.34	78.34	1.2195	3	3	0	4	4	14
79.44	79.44	1.2055	8	2	0	3	3	10
80.45	80.46	1.1927	0	3	1	6	5	21
82.24	82.24	1.1713	2	3	1	1	0	2
85.13	85.14	1.1388	8	0	2	3	2	9
85.48	85.40	1.1351	5	3	0	1	2	4
87.51	87.52	1.1138	10	1	1	0	1	2
87.56		1.1133	4	3	1	0		1
87.59		1.1131	1	0	3	0		1

Table B.10. Simulated X-ray powder pattern for $\text{Ca}_{1.1}\text{Sr}_{0.9}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.23	14.24	6.218	2	0	0	28	34	10
24.27	24.28	3.665	1	1	0	1	1	1
27.44	27.44	3.248	1	0	1	10	11	7
28.69	28.70	3.109	4	0	0	1	2	1
31.76	31.76	2.815	3	1	0	61	63	53
34.30	34.30	2.612	3	0	1	75	76	72
35.46	35.46	2.529	0	1	1	100	100	100
38.39	38.40	2.343	2	1	1	2	2	2
43.32	43.32	2.087	5	1	0	8	9	11
43.63	43.64	2.073	6	0	0	25	25	33
45.30	45.30	2.000	5	0	1	12	12	17
46.23	46.24	1.9620	4	1	1	4	4	6
47.37	47.38	1.9176	0	2	0	25	23	37
49.72	49.72	1.8324	2	2	0	2	2	4
54.50	54.50	1.6823	0	0	2	15	14	28
55.61	55.62	1.6513	1	2	1	2	2	3
56.32	56.34	1.6321	4	2	0	0	0	0
56.63	56.64	1.6239	2	0	2	2	2	3
57.09	57.44	1.6121	7	1	0	0	27	0
57.43		1.6032	6	1	1	30		59
59.41	59.42	1.5546	8	0	0	4	5	9
59.78	59.78	1.5458	3	2	1	27	24	56
60.51	60.50	1.5289	1	1	2	0	1	1
64.47	64.48	1.4441	3	1	2	17	14	39
66.36	66.36	1.4076	6	2	0	11	10	27
67.63	67.62	1.3842	5	2	1	6	5	15
71.13	71.14	1.3244	8	1	1	7	6	19
72.05	72.06	1.3097	5	1	2	3	3	9
72.27	72.28	1.3062	6	0	2	8	8	22
72.67	72.66	1.3000	9	1	0	3	3	8
74.12	74.12	1.2782	9	0	1	4	3	10
75.05	75.06	1.2646	0	2	2	9	8	27
76.54	76.54	1.2436	10	0	0	0	0	0
76.86	76.86	1.2392	2	2	2	1	1	3
78.18	78.18	1.2216	3	3	0	5	4	14
79.27	79.26	1.2076	8	2	0	3	3	10
80.27	80.26	1.1950	0	3	1	6	5	21
82.05	82.04	1.1736	2	3	1	0	0	2
82.88	82.88	1.1639	7	1	2	0	0	0
84.86	84.86	1.1417	8	0	2	3	2	9
85.29	85.30	1.1370	5	3	0	1	1	4
87.20	87.30	1.1170	1	0	3	0	1	1
87.29		1.1160	10	1	1	1		2
87.35		1.1155	4	3	1	0		1

Table B.11. Simulated X-ray powder pattern for CaSrCuO_3

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	(DS)
14.21	14.22	6.229	2	0	0	25	31	9
24.22	24.24	3.671	1	1	0	1	1	0
27.34	27.36	3.259	1	0	1	9	9	6
28.64	28.64	3.115	4	0	0	2	2	1
31.70	31.70	2.820	3	1	0	62	63	54
34.20	34.20	2.620	3	0	1	75	77	72
35.36	35.36	2.536	0	1	1	100	100	100
38.29	38.30	2.349	2	1	1	2	2	2
43.24	43.24	2.091	5	1	0	8	8	10
43.55	43.56	2.076	6	0	0	25	24	33
45.19	45.20	2.005	5	0	1	12	11	17
46.12	46.12	1.9667	4	1	1	4	4	6
47.28	47.28	1.9208	0	2	0	25	23	37
49.63	49.62	1.8355	2	2	0	2	2	4
54.29	54.30	1.6882	0	0	2	15	14	28
55.49	55.48	1.6548	1	2	1	1	1	3
56.22	56.42	1.6349	4	2	0	0	2	0
56.42		1.6295	2	0	2	1		3
56.98	57.30	1.6150	7	1	0	0	27	0
57.30		1.6067	6	1	1	30		59
59.29	59.30	1.5574	8	0	0	4	5	9
59.64	59.64	1.5491	3	2	1	27	24	57
60.29	60.28	1.5338	1	1	2	0	1	0
62.53	62.52	1.4842	4	0	2	0	0	0
64.25	64.26	1.4485	3	1	2	17	15	39

Table B.12. Simulated X-ray powder pattern for $\text{Ca}_{0.9}\text{Sr}_{1.1}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
14.18	14.20	6.241	2	0	0	23	28	8
24.18	24.20	3.677	1	1	0	0	0	0
27.25	27.26	3.270	1	0	1	8	8	6
28.58	28.60	3.120	4	0	0	2	2	2
31.65	31.66	2.825	3	1	0	62	64	54
34.10	34.10	2.627	3	0	1	76	77	72
35.26	35.26	2.543	0	1	1	100	100	100
38.18	38.18	2.355	2	1	1	2	2	2
43.16	43.16	2.094	5	1	0	8	8	10
43.47	43.46	2.080	6	0	0	25	24	33
45.07	45.08	2.010	5	0	1	11	11	16
46.00	46.00	1.9713	4	1	1	5	5	7
47.20	47.20	1.9241	0	2	0	25	24	37
49.54	49.54	1.8387	2	2	0	2	2	3
54.09	54.08	1.6942	0	0	2	15	14	28
55.36	55.36	1.6583	1	2	1	1	1	2
56.11	56.22	1.6377	4	2	0	0	2	1
56.21		1.6350	2	0	2	1		3
56.87	57.16	1.6178	7	1	0	0	27	1
57.16		1.6102	6	1	1	30		59
59.17	59.18	1.5602	8	0	0	4	5	9
59.50	59.50	1.5523	3	2	1	27	25	57
60.08	59.66	1.5388	1	1	2	0	15	0
62.31	62.32	1.4889	4	0	2	0	0	0
64.03	64.04	1.4530	3	1	2	17	15	40
66.10	66.10	1.4125	6	2	0	11	10	27
67.32	67.32	1.3898	5	2	1	6	5	14
70.79	70.80	1.3299	8	1	1	7	6	19
71.58	71.58	1.3172	5	1	2	3	3	9
71.80	71.80	1.3137	6	0	2	8	8	22
72.37	72.38	1.3047	9	1	0	3	3	8
73.76	73.76	1.2835	9	0	1	3	3	10
74.57	74.58	1.2715	0	2	2	9	8	28
76.22	76.38	1.2481	10	0	0	0	1	0
76.38		1.2459	2	2	2	1		3
77.87	77.86	1.2258	3	3	0	5	4	14
78.94	78.94	1.2118	8	2	0	3	3	10
79.90	79.90	1.1996	0	3	1	6	5	21
81.67	81.68	1.1781	2	3	1	0	0	1
81.71		1.1775	4	2	2	0		0
82.35	82.34	1.1701	7	1	2	0	0	1
84.32	84.32	1.1477	8	0	2	3	2	9
84.93	84.94	1.1409	5	3	0	1	1	3
86.44	86.44	1.1249	1	0	3	0	0	0
86.86	86.86	1.1205	10	1	1	1	1	3
86.93		1.1197	4	3	1	0		1
89.93	89.94	1.0900	3	0	3	4	3	15

Table B.13. Simulated X-ray powder pattern for $\text{Ca}_{0.8}\text{Sr}_{1.2}\text{CuO}_3$

[illegible]

Table B.14. Simulated X-ray powder pattern for $\text{Ca}_{0.7}\text{Sr}_{1.3}\text{CuO}_3$

[illegible]

Table B.15. Simulated X-ray powder pattern for $\text{Ca}_{0.6}\text{Sr}_{1.4}\text{CuO}_3$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.10	14.12	6.274	2	0	0	18	22	6
26.97	26.98	3.303	1	0	1	5	5	3
28.43	28.44	3.137	4	0	0	3	3	2
31.48	31.48	2.840	3	1	0	64	66	56
33.80	33.80	2.650	3	0	1	76	77	73
34.97	34.98	2.564	0	1	1	100	100	100
37.88	37.88	2.373	2	1	1	1	1	1
42.92	42.92	2.105	5	1	0	7	8	9
43.22	43.22	2.092	6	0	0	24	23	32
44.73	44.74	2.024	5	0	1	11	10	15
45.66	45.66	1.9852	4	1	1	6	6	9
46.95	46.96	1.9338	0	2	0	25	23	37
49.27	49.28	1.8480	2	2	0	2	1	3
53.48	53.48	1.7121	0	0	2	15	14	28
54.98	54.98	1.6689	1	2	1	1	1	1
55.60	55.60	1.6517	2	0	2	1	1	2
55.80	55.76	1.6462	4	2	0	1	1	1
56.54	56.76	1.6265	7	1	0	1	27	1
56.76		1.6206	6	1	1	30		59
58.03	58.02	1.5882	7	0	1	0	0	0
58.82	58.82	1.5686	8	0	0	4	5	9
59.10	59.10	1.5620	3	2	1	28	25	59
61.67	61.66	1.5029	4	0	2	0	0	1
63.39	63.38	1.4662	3	1	2	18	15	42
65.71	65.72	1.4199	6	2	0	11	9	27

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
66.86	66.86	1.3983	5	2	1	5	4	13
70.30	70.30	1.3380	8	1	1	7	6	19
70.89	70.90	1.3283	5	1	2	3	3	8
71.10	71.10	1.3248	6	0	2	8	8	23
71.93	71.92	1.3117	9	1	0	3	2	8
73.24	73.24	1.2914	9	0	1	3	3	10
73.87	73.88	1.2819	0	2	2	10	8	28
75.66	75.66	1.2559	2	2	2	1	1	2
75.73		1.2549	10	0	0	0		1
77.40	77.40	1.2320	3	3	0	5	4	15
77.75	77.62	1.2273	7	2	1	0	2	1
78.44	78.44	1.2182	8	2	0	3	3	10
79.35	79.36	1.2065	0	3	1	7	5	22
80.95	80.96	1.1866	4	2	2	0	0	1
81.11	81.10	1.1848	2	3	1	0	0	1
81.57	81.58	1.1792	7	1	2	0	0	1
83.52	83.52	1.1566	8	0	2	2	2	9
84.40	84.40	1.1467	5	3	0	1	1	3
86.22	86.22	1.1271	10	1	1	1	1	4
86.32		1.1261	4	3	1	0		2
88.78	88.78	1.1011	3	0	3	4	3	15
89.44	89.46	1.0947	0	1	3	5	6	18
89.49		1.0942	11	1	0	3		10
89.63	89.62	1.0929	6	2	2	8	8	31

Table B.16. Simulated X-ray powder pattern for $\text{Ca}_{0.5}\text{Sr}_{1.5}\text{CuO}_3$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.08	14.08	6.286	2	0	0	16	20	6	65.58	65.58	1.4223	6	2	0	11	9	27
24.02	24.02	3.702	1	1	0	0	0	0	66.70	66.70	1.4011	5	2	1	5	4	13
26.88	26.88	3.315	1	0	1	4	4	3	70.13	70.14	1.3408	8	1	1	7	6	19
28.37	28.38	3.143	4	0	0	3	4	3	70.66	70.66	1.3320	5	1	2	3	3	8
31.42	31.42	2.845	3	1	0	65	65	56	70.87	70.88	1.3285	6	0	2	8	8	23
33.70	33.72	2.657	3	0	1	77	76	73	71.78	71.78	1.3140	9	1	0	3	2	8
34.87	34.88	2.571	0	1	1	100	100	100	73.07	73.06	1.2940	9	0	1	3	3	10
37.78	37.78	2.379	2	1	1	1	1	1	73.64	73.64	1.2853	0	2	2	10	8	29
42.84	42.84	2.109	5	1	0	7	7	9	75.43	75.42	1.2593	2	2	2	1	1	2
43.14	43.14	2.095	6	0	0	24	23	32	75.58	75.62	1.2571	10	0	0	0	0	1
44.62	44.62	2.029	5	0	1	10	10	14	77.25	77.24	1.2341	3	3	0	5	4	15
45.55	45.56	1.9898	4	1	1	7	7	10	77.57	77.48	1.2297	7	2	1	0	2	1
46.87	46.86	1.9370	0	2	0	24	22	37	78.28	78.28	1.2203	8	2	0	3	3	10
49.18	49.18	1.8511	2	2	0	1	1	2	79.17	79.18	1.2088	0	3	1	7	5	22
53.28	53.28	1.7181	0	0	2	16	14	29	80.70	80.70	1.1897	4	2	2	0	0	1
54.85	54.86	1.6724	1	2	1	1	1	1	80.92	80.92	1.1870	2	3	1	0	0	1
55.39	55.40	1.6573	2	0	2	1	1	2	81.32	81.32	1.1822	7	1	2	0	0	2
55.70	55.70	1.6490	4	2	0	1	1	1	83.26	83.26	1.1595	8	0	2	2	2	9
56.43	56.62	1.6294	7	1	0	1	26	1	84.22	84.22	1.1487	5	3	0	1	1	3
56.63		1.6241	6	1	1	30		60	86.01	86.02	1.1293	10	1	1	1	1	4
57.89	57.90	1.5916	7	0	1	0	0	0	86.12		1.1282	4	3	1	0		2
58.71	58.72	1.5714	8	0	0	4	5	9	88.41	88.40	1.1048	3	0	3	4	3	15
58.96	58.96	1.5652	3	2	1	28	25	59	89.06	89.06	1.0984	0	1	3	5	4	19
61.46	61.46	1.5075	4	0	2	0	0	1	89.29	89.34	1.0962	11	1	0	3	9	10
63.17	63.18	1.4706	3	1	2	18	15	42	89.35		1.0956	6	2	2	8		31

Table B.17. Simulated X-ray powder pattern for $\text{Ca}_{0.4}\text{Sr}_{1.6}\text{CuO}_3$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.05	14.06	6.297	2	0	0	15	18	5	65.45	65.46	1.4248	6	2	0	11	9	27
23.98	23.98	3.708	1	1	0	0	0	0	63.55	66.56	1.4039	5	2	1	5	4	12
26.79	26.80	3.326	1	0	1	3	4	2	69.97	69.98	1.3435	8	1	1	7	6	19
28.32	28.34	3.148	4	0	0	4	4	3	70.44	70.44	1.3357	5	1	2	3	3	8
31.37	31.38	2.850	3	1	0	65	66	57	70.65	70.64	1.3322	6	0	2	8	8	23
33.61	33.62	2.664	3	0	1	77	77	74	71.63	71.64	1.3164	9	1	0	3	2	8
34.78	34.78	2.578	0	1	1	100	100	100	72.89	72.90	1.2966	9	0	1	3	3	10
37.68	37.68	2.385	2	1	1	1	1	1	73.41	73.42	1.2888	0	2	2	10	8	29
42.77	42.78	2.113	5	1	0	6	7	9	75.19	75.20	1.2626	2	2	2	1	1	2
43.06	43.06	2.099	6	0	0	24	23	32	75.42	75.42	1.2594	10	0	0	0	1	1
44.51	44.52	2.034	5	0	1	10	9	14	77.09	77.10	1.2362	3	3	0	5	4	15
45.44	45.44	1.9944	4	1	1	7	7	11	77.39	77.32	1.2321	7	2	1	0	2	1
46.78	46.78	1.9403	0	2	0	24	23	37	78.12	78.12	1.2225	8	2	0	3	3	10
49.09	49.10	1.8542	2	2	0	1	1	2	78.99	79.00	1.2111	0	3	1	7	5	22
53.08	53.08	1.7240	0	0	2	16	14	29	80.46	80.46	1.1927	4	2	2	0	0	1
54.73	54.72	1.6759	1	2	1	0	0	1	80.74	80.72	1.1893	2	3	1	0	0	1
55.19	55.20	1.6628	2	0	2	1	1	2	81.07	81.06	1.1853	7	1	2	1	0	2
55.59	55.60	1.6518	4	2	0	1	1	1	83.00	83.00	1.1625	8	0	2	2	2	9
56.32	56.50	1.6322	7	1	0	1	27	2	84.05	84.04	1.1506	5	3	0	1	1	3
56.49		1.6276	6	1	1	30		59	85.80	85.80	1.1315	10	1	1	1	1	4
57.75	57.76	1.5951	7	0	1	0	0	1	85.92		1.1303	4	3	1	1		2
58.59	58.60	1.5742	8	0	0	4	5	9	88.03	88.04	1.1085	3	0	3	4	3	15
58.83	58.82	1.5685	3	2	1	28	25	59	88.69	88.70	1.1020	0	1	3	5	4	19
61.25	61.24	1.5122	4	0	2	0	0	1	89.08	89.08	1.0983	6	2	2	8	9	31
62.96	62.96	1.4751	3	1	2	18	16	43	89.09		1.0981	11	1	0	3		10

Table B.18. Simulated X-ray powder pattern for $\text{Ca}_{0.3}\text{Sr}_{1.7}\text{CuO}_3$

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
14.03	14.04	6.308	2	0	0	14	17	5	65.33	65.32	1.4272	6	2	0	11	9	27
23.94	23.94	3.715	1	1	0	0	0	0	66.40	66.40	1.4067	5	2	1	5	4	12
26.69	26.70	3.337	1	0	1	3	3	2	69.81	69.80	1.3462	8	1	1	7	6	19
28.27	28.28	3.154	4	0	0	4	4	3	70.21	70.22	1.3394	5	1	2	3	3	8
31.31	31.32	2.854	3	1	0	65	67	57	70.42	70.42	1.3359	6	0	2	8	8	23
33.51	33.52	2.672	3	0	1	77	79	74	71.48	71.48	1.3187	9	1	0	3	2	8
34.68	34.68	2.584	0	1	1	100	100	100	72.72	72.72	1.2992	9	0	1	3	3	10
37.58	37.58	2.391	2	1	1	1	1	1	73.18	73.18	1.2922	0	2	2	10	8	29
42.69	42.70	2.116	5	1	0	6	7	8	74.96	74.96	1.2659	2	2	2	1	1	2
42.98	42.98	2.103	6	0	0	23	23	32	75.26	75.20	1.2616	10	0	0	0	0	1
44.40	44.40	2.039	5	0	1	10	9	14	76.94	76.94	1.2382	3	3	0	5	4	16
45.33	45.34	1.9990	4	1	1	8	8	12	77.21	77.16	1.2345	7	2	1	0	2	1
46.70	46.70	1.9435	0	2	0	24	23	37	77.96	77.96	1.2246	8	2	0	3	2	10
49.00	49.00	1.8573	2	2	0	1	1	2	78.82	78.82	1.2134	0	3	1	7	5	22
52.88	52.88	1.7300	0	0	2	16	14	29	80.21	80.22	1.1957	4	2	2	0	0	1
54.60	54.60	1.6794	1	2	1	0	0	1	80.55	80.54	1.1915	2	3	1	0	0	1
54.99	55.00	1.6684	2	0	2	1	1	2	80.82	80.82	1.1883	7	1	2	1	1	2
55.49	55.50	1.6546	4	2	0	1	1	2	82.74	82.74	1.1655	8	0	2	2	2	9
56.21	56.36	1.6351	7	1	0	1	27	2	83.87	83.88	1.1526	5	3	0	1	1	3
56.36		1.6311	6	1	1	30		60	85.60	85.60	1.1338	10	1	1	1	1	5
57.62	57.62	1.5985	7	0	1	0	1	1	85.72	85.70	1.1325	4	3	1	1	1	2
58.48	58.50	1.5771	8	0	0	4	6	9	87.67	87.66	1.1122	3	0	3	4	3	15
58.70	58.70	1.5717	3	2	1	28	26	60	88.32	88.32	1.1057	0	1	3	5	4	19
61.04	61.04	1.5168	4	0	2	1	1	1	88.80	88.80	1.1009	6	2	2	8	7	31
62.75	62.76	1.4795	3	1	2	18	16	43	88.89		1.1001	11	1	0	3		10

Table B.19. Simulated X-ray powder pattern for $\text{Ca}_{0.2}\text{Sr}_{1.8}\text{CuO}_3$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
13.98	13.98	6.331	2	0	0	13	15	4
23.89	23.90	3.721	1	1	0	0	1	0
26.60	26.60	3.348	1	0	1	2	2	2
28.17	28.18	3.165	4	0	0	5	5	3
31.23	31.24	2.862	3	1	0	66	68	58
33.39	33.40	2.681	3	0	1	78	79	74
34.59	34.60	2.591	0	1	1	100	100	100
37.47	37.48	2.398	2	1	1	1	1	1
42.55	42.56	2.123	5	1	0	6	7	8
42.82	42.82	2.110	6	0	0	23	23	32
44.23	44.24	2.046	5	0	1	9	9	13
45.18	45.18	2.005	4	1	1	8	8	12
46.62	46.62	1.9467	0	2	0	24	23	37
48.91	48.92	1.8607	2	2	0	1	1	2
52.69	52.68	1.7359	0	0	2	16	14	29
54.48	54.48	1.6829	1	2	1	0	0	1
54.79	54.80	1.6741	2	0	2	1	1	2
55.36	55.36	1.6582	4	2	0	1	1	2
56.01	56.16	1.6404	7	1	0	1	27	2
56.17		1.6363	6	1	1	30		60
57.40	57.40	1.6041	7	0	1	0	1	1
58.25	58.26	1.5827	8	0	0	4	5	8
58.55	58.54	1.5753	3	2	1	28	25	60
60.81	60.80	1.5221	4	0	2	1	1	1
62.53	62.54	1.4842	3	1	2	18	16	44
65.14	65.14	1.4309	6	2	0	11	9	27
66.21	66.22	1.4103	5	2	1	5	4	12
69.54	69.54	1.3507	8	1	1	7	6	19
69.95	69.96	1.3438	5	1	2	3	3	7
70.14	70.14	1.3406	6	0	2	8	8	23
71.21	71.22	1.3231	9	1	0	3	2	8
72.43	72.42	1.3039	9	0	1	3	3	10
72.96	72.96	1.2956	0	2	2	10	8	29
74.73	74.72	1.2693	2	2	2	1	1	2
74.94	74.94	1.2661	10	0	0	0	1	1
76.77	76.78	1.2405	3	3	0	5	4	16
76.96	77.00	1.2380	7	2	1	0	3	1
77.70	77.70	1.2280	8	2	0	3	2	10
78.64	78.64	1.2157	0	3	1	7	6	22
79.94	79.94	1.1991	4	2	2	0	0	2
80.36	80.50	1.1938	2	3	1	0	1	1
80.49		1.1923	7	1	2	1		2
82.39	82.40	1.1696	8	0	2	2	2	9
83.66	83.66	1.1550	5	3	0	1	1	3
85.24	85.24	1.1376	10	1	1	1	1	5
85.50	85.50	1.1348	4	3	1	1	1	3
87.29	87.28	1.1161	3	0	3	4	3	16
87.96	87.96	1.1093	0	1	3	5	4	19
88.48	88.48	1.1041	6	2	2	8	8	31
88.51		1.1038	11	1	0	3		10
89.65	89.66	1.0927	2	1	3	0	3	1
89.67		1.0926	11	0	1	3		12

Table B.20. Simulated X-ray powder pattern for $\text{Ca}_{0.1}\text{Sr}_{1.9}\text{CuO}_3$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
13.98	13.98	6.331	2	0	0	12	14	4
23.85	23.86	3.727	1	1	0	1	1	0
26.51	26.52	3.359	1	0	1	2	2	1
28.17	28.18	3.165	4	0	0	5	5	4
31.20	31.20	2.864	3	1	0	66	67	58
33.32	33.32	2.687	3	0	1	78	78	74
34.49	34.50	2.598	0	1	1	100	100	100
37.38	37.38	2.404	2	1	1	0	0	0
42.53	42.54	2.124	5	1	0	6	7	8
42.82	42.82	2.110	6	0	0	23	22	31
44.18	44.18	2.048	5	0	1	9	9	13
45.11	45.12	2.008	4	1	1	9	8	13
46.54	46.54	1.9500	0	2	0	24	22	37
48.83	48.84	1.8636	2	2	0	1	1	2
52.49	52.50	1.7419	0	0	2	16	14	29
54.36	54.36	1.6864	1	2	1	0	0	0
54.60	54.60	1.6795	2	0	2	1	1	1
55.29	55.30	1.6602	4	2	0	1	1	2
56.00	56.10	1.6409	7	1	0	1	27	2
56.10		1.6380	6	1	1	29		60
57.35	57.36	1.6053	7	0	1	0	1	1
58.25	58.44	1.5827	8	0	0	4	26	8
58.43		1.5781	3	2	1	28		61
60.63	60.64	1.5261	4	0	2	1	1	2
62.34	62.34	1.4883	3	1	2	19	16	44
65.08	65.08	1.4321	6	2	0	10	9	27
66.11	66.10	1.4123	5	2	1	4	4	12
69.49	69.48	1.3516	8	1	1	7	6	18
69.77	69.70	1.3468	5	1	2	3	4	7
69.98	69.98	1.3434	6	0	2	8	8	23

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
71.19	71.20	1.3234	9	1	0	3	2	8
72.39	72.38	1.3045	9	0	1	3	3	10
72.74	72.74	1.2991	0	2	2	10	8	29
74.50	74.50	1.2725	2	2	2	0	0	2
74.94	74.94	1.2661	10	0	0	0	0	1
76.64	76.64	1.2424	3	3	0	5	4	16
76.86	76.86	1.2394	7	2	1	0	3	1
77.64	77.64	1.2289	8	2	0	3	2	9
78.46	78.46	1.2179	0	3	1	7	5	22
79.73	79.72	1.2018	4	2	2	1	0	2
80.19	80.32	1.1960	2	3	1	0	1	1
80.32		1.1944	7	1	2	1		3
82.23	82.24	1.1714	8	0	2	2	2	9
83.53	83.52	1.1565	5	3	0	1	1	3
85.18	85.18	1.1382	10	1	1	1	1	5
85.32	85.32	1.1367	4	3	1	1	1	3
86.94	86.94	1.1197	3	0	3	4	3	16
87.60	87.60	1.1130	0	1	3	5	4	19
88.26	88.26	1.1063	6	2	2	8	6	31
88.49	88.52	1.1040	11	1	0	3	5	10
89.29	89.30	1.0962	2	1	3	0	0	1
89.63	89.62	1.0929	11	0	1	3	2	12

Table B.21. Simulated X-ray powder pattern for Sr_2CuO_3

[illegible]

APPENDIX C: $(\text{Ca,Sr})_{14}\text{Cu}_{24}\text{O}_{41}$

Table C.1. Simulated X-ray powder pattern for $\text{Sr}_{14}\text{Cu}_{24}\text{O}_{41}$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
13.20	13.22	6.700	0	2	0	2	2	1	47.99		1.8944	0	2	14	7		11
15.44	15.44	5.734	2	0	0	1	2	1	48.73	48.72	1.8674	2	0	14	3	3	6
16.36	16.36	5.415	1	1	4	0	0	0	49.55	49.56	1.8382	6	2	0	11	10	20
20.37	20.38	4.357	2	2	0	0	0	0	50.04	50.30	1.8214	1	7	4	0	17	0
22.56	22.56	3.939	2	2	3	1	1	1	50.29		1.8129	5	3	7	20		37
24.73	24.74	3.598	1	1	7	9	9	7	50.71	50.70	1.7988	2	2	14	3	3	6
24.95		3.566	1	3	4	0		0	51.85	51.86	1.7619	4	6	0	1	1	1
26.59	26.60	3.350	0	4	0	15	15	13	52.22	52.22	1.7503	5	1	10	4	4	9
30.89	30.90	2.893	2	4	0	100	100	100	53.25	53.26	1.7189	3	5	10	3	3	6
31.17	31.20	2.867	4	0	0	10	85	10	53.77	53.76	1.7035	1	7	7	4	4	8
31.19		2.865	1	3	7	73		74	54.76	54.76	1.6750	0	8	0	14	12	29
32.41	32.42	2.760	2	4	3	0	1	0	55.29	55.28	1.6602	6	4	0	1	1	2
33.27	33.28	2.691	3	1	7	59	56	65	55.96	55.96	1.6418	5	3	10	2	2	5
33.98	33.98	2.636	4	2	0	10	13	12	56.36	56.36	1.6311	2	4	14	15	13	34
33.99		2.635	1	1	10	3		3	56.54	56.52	1.6265	4	0	14	2	9	4
36.78	36.78	2.441	1	5	4	0	0	0	57.25	57.26	1.6078	2	8	0	0	0	0
38.44	38.44	2.340	3	3	7	6	5	7	57.78	57.78	1.5944	5	5	7	6	5	13
39.08	39.08	2.303	1	3	10	3	3	4	58.33	58.34	1.5806	4	2	14	2	2	4
40.35	40.36	2.233	0	6	0	3	3	4	58.74	58.74	1.5706	3	7	7	14	12	33
40.80	40.80	2.210	3	1	10	9	9	13	59.21	59.20	1.5593	1	7	10	1	1	3
41.42	41.44	2.178	4	4	0	15	33	22	61.62	61.62	1.5038	7	1	7	1	1	2
41.44		2.177	1	5	7	22		31	62.75	62.76	1.4795	0	6	14	5	4	13
43.45	43.46	2.081	2	6	0	2	2	3	63.00	62.94	1.4743	5	5	10	2	3	4
44.60	44.60	2.030	2	6	3	0	0	1	63.53	63.54	1.4631	4	4	14	11	9	28
45.24	45.24	2.003	3	3	10	6	6	10	63.91	64.08	1.4554	3	7	10	1	6	3
45.91	45.92	1.9750	0	0	14	17	16	29	64.07		1.4522	6	6	0	7		19
46.23	46.22	1.9622	5	1	7	2	3	3									
46.36		1.9570	5	3	4	0		0									
47.53	47.54	1.9115	6	0	0	10	9	18									
47.89	47.98	1.8979	1	5	10	1	6	1									

Table C.2. Simulated X-ray powder pattern for $\text{Sr}_{13}\text{CaCu}_{24}\text{O}_{41}$

20	PEAK	d	h	k	l	(INT)	(PK)	(DS)	20	PEAK	d	h	k	l	(INT)	(PK)	(DS)
13.25	13.26	6.677	0	2	0	2	3	1	47.98		1.8945	0	2	14	7		12
15.47	15.48	5.724	2	0	0	1	1	0	48.72	48.72	1.8675	2	0	14	3	3	6
16.37	16.38	5.411	1	1	4	0	0	0	49.65	49.66	1.8346	6	2	0	12	10	21
20.42	20.44	4.346	2	2	0	0	0	0	50.20	50.38	1.8157	1	7	4	0	17	0
22.60	22.62	3.931	2	2	3	1	1	1	50.38		1.8099	5	3	7	20		37
24.73	24.74	3.597	1	1	7	8	8	6	50.72	50.72	1.7985	2	2	14	3	4	6
25.01		3.558	1	3	4	0		0	52.01	52.02	1.7569	4	6	0	1	1	1
26.68	26.68	3.339	0	4	0	17	17	14	52.28	52.28	1.7485	5	1	10	4	4	9
30.98	31.00	2.884	2	4	0	100	100	100	53.34	53.34	1.7161	3	5	10	3	3	6
31.23	31.24	2.862	4	0	0	10	87	10	53.92	53.92	1.6989	1	7	7	4	3	8
31.24		2.861	1	3	7	73		73	54.96	54.96	1.6693	0	8	0	14	12	29
32.51	32.52	2.752	2	4	3	0	1	0	55.42	55.42	1.6565	6	4	0	1	1	1
33.30	33.30	2.689	3	1	7	60	57	65	56.04	56.04	1.6397	5	3	10	2	2	5
33.99	34.06	2.636	1	1	10	3	13	4	56.41	56.42	1.6299	2	4	14	15	13	33
34.05		2.631	4	2	0	11		12	56.56	56.56	1.6259	4	0	14	2	9	3
36.89	36.90	2.434	1	5	4	0	0	0	57.91	57.92	1.5911	5	5	7	6	5	13
38.50	38.50	2.336	3	3	7	5	5	7	58.37	58.36	1.5797	4	2	14	2	2	4
39.11	39.12	2.301	1	3	10	3	3	5	58.91	58.90	1.5665	3	7	7	14	11	32
40.50	40.50	2.226	0	6	0	3	3	4	59.35	59.34	1.5558	1	7	10	1	2	3
40.82	40.82	2.209	3	1	10	10	9	13	61.73	61.74	1.5015	7	1	7	1	0	1
41.53	41.54	2.173	4	4	0	15	33	21	62.85	62.84	1.4775	0	6	14	5	4	13
41.53		2.173	1	5	7	22		31	63.12	63.02	1.4718	5	5	10	2	3	5
43.60	43.60	2.074	2	6	0	2	2	3	63.60	63.60	1.4617	4	4	14	11	9	27
44.74	44.76	2.024	2	6	3	0	1	1	64.07	64.06	1.4522	3	7	10	1	1	3
45.29	45.30	2.001	3	3	10	7	6	11									
45.90	45.90	1.9756	0	0	14	18	16	29									
46.29	46.28	1.9596	5	1	7	1	2	2									
46.46		1.9531	5	3	4	0		0									
47.62	47.62	1.9080	6	0	0	10	9	18									
47.97	47.98	1.8948	1	5	10	1	7	1									

Table C.5. Simulated X-ray powder pattern for $\text{Sr}_{10}\text{Ca}_4\text{Cu}_{24}\text{O}_{41}$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
13.46	13.46	6.575	0	2	0	3	4	1
16.48	16.50	5.374	1	1	4	0	0	0
20.61	20.62	4.306	2	2	0	0	1	0
22.80	22.80	3.897	2	2	3	1	1	1
24.88	24.90	3.575	1	1	7	5	5	4
25.31	25.32	3.516	1	3	4	0	0	0
27.10	27.10	3.287	0	4	0	24	22	20
31.38	31.40	2.849	4	0	0	8	100	8
31.39		2.847	2	4	0	100		100
31.54	31.52	2.834	1	3	7	70	84	71
32.91	33.48	2.719	2	4	3	0	49	0
33.48		2.674	3	1	7	60		65
34.19	34.28	2.621	1	1	10	4	12	4
34.28		2.614	4	2	0	12		13
37.42	37.42	2.401	1	5	4	0	0	0
38.82	38.82	2.318	3	3	7	3	3	4
39.44	39.44	2.283	1	3	10	4	3	5
41.06	41.06	2.197	3	1	10	11	9	15
41.15	41.14	2.192	0	6	0	3	8	4
41.93	42.06	2.153	4	4	0	14	22	20
42.06		2.147	1	5	7	22		31
44.24	44.24	2.046	2	6	0	2	1	3
45.39	45.64	1.9965	2	6	3	0	6	1
45.64		1.9861	3	3	10	7		12
46.16	46.16	1.9650	0	0	14	18	13	29
46.55	46.54	1.9496	5	1	7	1	1	2
46.79		1.9398	5	3	4	0		0
47.86	47.86	1.8990	6	0	0	10	7	17
47.98	47.98	1.8944	3	5	7	0	5	0
48.30	48.30	1.8827	0	2	14	8	6	14
48.51	48.42	1.8751	1	5	10	1	4	2
49.00	49.00	1.8576	2	0	14	2	2	4
49.95	49.96	1.8244	6	2	0	14	9	24
50.74	50.74	1.7979	5	3	7	19	13	35
50.99	50.86	1.7897	1	7	4	0	9	0
51.05	51.04	1.7876	2	2	14	4	4	7
52.57	52.58	1.7395	5	1	10	5	4	10
52.65		1.7370	4	6	0	1		2
53.89	53.90	1.7000	3	5	10	3	2	7
54.71	54.72	1.6764	1	7	7	3	2	6
55.87	55.90	1.6444	6	4	0	0	9	1
55.89		1.6437	0	8	0	14		29
56.43	56.44	1.6292	5	3	10	3	2	5
56.88	56.88	1.6175	4	0	14	1	10	2
56.89		1.6173	2	4	14	14		31
58.46	58.46	1.5774	5	5	7	5	4	12
58.74	58.62	1.5706	4	2	14	2	2	4
59.69	59.70	1.5478	3	7	7	13	8	30
60.15	60.14	1.5372	1	7	10	1	1	3
62.07	62.08	1.4941	7	1	7	0	0	1
63.54	63.54	1.4631	0	6	14	6	4	14
63.70	63.70	1.4598	5	5	10	2	3	5

Table C.6. Simulated X-ray powder pattern for $\text{Sr}_9\text{Ca}_5\text{Cu}_{24}\text{O}_{41}$

20	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
13.55	13.56	6.530	0	2	0	3	3	2
15.56	15.58	5.690	2	0	0	0	0	0
16.53	16.54	5.359	1	1	4	0	0	0
20.69	20.70	4.290	2	2	0	1	0	0
22.88	22.88	3.884	2	2	3	1	1	1
24.95	24.96	3.567	1	1	7	4	3	3
25.44	25.44	3.498	1	3	4	0	0	0
27.29	27.30	3.265	0	4	0	27	21	23
31.42	31.58	2.845	4	0	0	8	93	8
31.57		2.832	2	4	0	100		100
31.67	31.66	2.823	1	3	7	69	100	70
33.09	33.56	2.705	2	4	3	0	46	0
33.55		2.669	3	1	7	60		65
34.27	34.36	2.614	1	1	10	4	12	4
34.36		2.608	4	2	0	12		14
37.66	37.66	2.387	1	5	4	0	0	0
38.95	38.96	2.311	3	3	7	3	2	4
39.58	39.58	2.275	1	3	10	4	3	5
41.14	41.14	2.192	3	1	10	12	9	16
41.45	41.46	2.177	0	6	0	3	3	4
42.09	42.10	2.145	4	4	0	13	11	19
42.29	42.30	2.135	1	5	7	22	17	31
44.53	44.54	2.033	2	6	0	2	1	2
45.68	45.78	1.9846	2	6	3	0	6	1
45.78		1.9804	3	3	10	8		12
46.27	46.26	1.9607	0	0	14	18	13	29
46.62	46.38	1.9465	5	1	7	1	8	1
46.91		1.9351	5	3	4	0		0
47.92	47.92	1.8967	6	0	0	10	7	17
48.21	48.04	1.8861	3	5	7	0	5	1

Table C.7. Simulated X-ray powder pattern for $\text{Sr}_8\text{Ca}_6\text{Cu}_{24}\text{O}_{41}$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
13.60	13.62	6.505	0	2	0	4	3	2
15.57	15.58	5.688	2	0	0	1	1	0
16.54	16.56	5.354	1	1	4	0	0	0
20.73	20.74	4.282	2	2	0	1	0	0
22.91	22.92	3.878	2	2	3	1	1	1
24.96	24.98	3.564	1	1	7	3	2	3
25.51	25.52	3.489	1	3	4	0	0	0
27.40	27.40	3.253	0	4	0	30	21	25
31.43	31.72	2.844	4	0	0	7	100	7
31.66		2.823	2	4	0	100		100
31.73		2.817	1	3	7	68		69
33.18	33.58	2.698	2	4	3	0	41	0
33.57		2.667	3	1	7	60		64
34.29	34.40	2.613	1	1	10	4	11	4
34.39		2.606	4	2	0	13		14
37.78	37.78	2.379	1	5	4	0	0	0
39.00	39.00	2.308	3	3	7	2	2	3
39.64	39.64	2.272	1	3	10	4	3	6
41.16	41.16	2.191	3	1	10	12	8	17
41.62	41.62	2.168	0	6	0	3	2	4
42.18	42.18	2.141	4	4	0	13	9	18
42.41	42.42	2.130	1	5	7	22	15	31
44.69	44.70	2.026	2	6	0	2	1	2
45.83	45.84	1.9782	3	3	10	8	6	13
45.84		1.9781	2	6	3	0		1
46.28	46.28	1.9600	0	0	14	18	12	29
46.65	46.40	1.9455	5	1	7	1	8	1
46.97		1.9330	5	3	4	0		0
47.95	47.94	1.8958	6	0	0	10	6	17
48.32	48.46	1.8820	3	5	7	1	6	1
48.47		1.8767	0	2	14	9		15
48.86	48.86	1.8626	1	5	10	1	1	2
49.13	49.12	1.8531	2	0	14	2	1	3
50.08	50.08	1.8201	6	2	0	15	10	27
50.92	50.92	1.7918	5	3	7	19	12	34
51.22	51.20	1.7822	2	2	14	4	4	7
51.53	51.34	1.7720	1	7	4	0	2	0
52.69	52.70	1.7357	5	1	10	6	3	11
53.07	53.06	1.7243	4	6	0	1	1	2
54.23	54.22	1.6901	3	5	10	4	2	7
54.63	54.62	1.6787	0	4	14	0	0	0
55.25	55.24	1.6614	1	7	7	2	1	5
56.11	56.54	1.6379	6	4	0	0	9	0
56.55		1.6263	0	8	0	14		29
56.63		1.6239	5	3	10	3		6
57.02	57.16	1.6138	4	0	14	1	9	2
57.17		1.6101	2	4	14	14		29
58.79	58.80	1.5694	5	5	7	5	3	12
58.92	58.94	1.5663	4	2	14	2	3	4
60.22	60.22	1.5355	3	7	7	13	8	29
60.68	60.68	1.5249	1	7	10	1	1	3
62.20	62.20	1.4912	7	1	7	0	0	0
63.98	64.00	1.4540	0	6	14	6	4	14
64.04		1.4529	5	5	10	2		5

Table C.8. Simulated X-ray powder pattern for $\text{Sr}_7\text{Cu}_7\text{Cu}_{24}\text{O}_{41}$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
13.63	13.64	6.493	0	2	0	4	3	2
15.57	15.58	5.686	2	0	0	2	1	1
16.57	16.58	5.346	1	1	4	0	0	0
20.75	20.76	4.277	2	2	0	1	1	0
22.94	22.96	3.873	2	2	3	1	1	1
25.00	25.02	3.559	1	1	7	2	2	2
25.55	25.56	3.483	1	3	4	0	0	0
27.45	27.46	3.247	0	4	0	33	24	28
31.44	31.78	2.843	4	0	0	7	100	7
31.71		2.819	2	4	0	100		100
31.79		2.813	1	3	7	67		67
33.23	33.62	2.694	2	4	3	0	41	0
33.61		2.665	3	1	7	60		64
34.35	34.42	2.609	1	1	10	4	12	5
34.41		2.604	4	2	0	13		15
37.85	37.86	2.375	1	5	4	0	0	0
39.05	39.06	2.305	3	3	7	2	1	3
39.71	39.72	2.268	1	3	10	4	3	6
41.22	41.22	2.188	3	1	10	13	9	17
41.70	41.70	2.164	0	6	0	3	3	4
42.22	42.22	2.139	4	4	0	12	9	17
42.49	42.50	2.126	1	5	7	22	15	31
44.77	44.78	2.023	2	6	0	1	1	2
45.90	45.90	1.9755	3	3	10	8	6	13
45.92		1.9749	2	6	3	1		1
46.37	46.38	1.9566	0	0	14	18	12	29
46.68	46.48	1.9441	5	1	7	0	8	1
47.01		1.9315	5	3	4	0	0	
47.96	47.96	1.8952	6	0	0	10	7	17
48.40	48.56	1.8793	3	5	7	1	6	1
48.56		1.8734	0	2	14	10		16
48.95	48.94	1.8593	1	5	10	1	1	2
49.21	49.20	1.8501	2	0	14	2	1	3
50.10	50.10	1.8193	6	2	0	16	10	28
50.97	50.98	1.7902	5	3	7	19	12	33
51.31	51.30	1.7793	2	2	14	4	3	7
51.63	51.42	1.7688	1	7	4	0	2	0
52.75	52.74	1.7341	5	1	10	6	4	11
53.14	53.14	1.7220	4	6	0	1	1	2
54.32	54.32	1.6876	3	5	10	4	2	8
54.73	54.72	1.6758	0	4	14	0	0	1
55.35	55.36	1.6584	1	7	7	2	1	4
56.15	56.66	1.6367	6	4	0	0	10	0
56.66		1.6233	0	8	0	14		29
56.70		1.6222	5	3	10	3		6
57.10	57.26	1.6117	4	0	14	1	9	2
57.27		1.6074	2	4	14	13		28
58.86	58.86	1.5677	5	5	7	5	4	12
59.00	59.02	1.5642	4	2	14	2	3	4
60.33	60.32	1.5331	3	7	7	12	7	28
60.80	60.80	1.5222	1	7	10	2	1	4
62.24	62.24	1.4904	7	1	7	0	0	0

APPENDIX D: $(\text{Ca,Sr})\text{CuO}_2$

Table D.1. Simulated X-ray powder pattern for SrCuO₂

20	PEAK	d	h	k	l	l(NT)	l(PK)	l(DS)	20	PEAK	d	h	k	l	l(NT)	l(PK)	l(DS)
10.83	10.84	8.166	0	2	0	0	1	0	68.94	68.94	1.3609	0	12	0	2	2	5
21.75	21.76	4.083	0	4	0	16	18	9	69.92	69.92	1.3444	2	8	0	6	5	16
25.21	25.22	3.529	0	2	1	8	9	5	71.44	71.44	1.3194	2	0	2	10	9	29
25.50	25.50	3.490	1	1	0	15	17	10	73.07	73.08	1.2939	1	11	1	12	10	35
29.89	29.90	2.987	1	3	0	63	65	53	73.45	73.28	1.2882	0	2	3	0	6	1
31.64	31.64	2.825	0	4	1	56	56	50	73.63	73.64	1.2854	0	12	1	0	1	1
32.88	32.88	2.722	0	6	0	6	6	5	74.58	74.58	1.2715	2	8	1	4	4	13
34.40	34.40	2.605	1	1	1	100	100	100	75.70	75.80	1.2554	2	4	2	1	3	4
37.27	37.28	2.411	1	5	0	11	11	13	75.81		1.2538	0	10	2	3		8
37.86	37.86	2.374	1	3	1	11	11	13	76.31	76.32	1.2469	1	9	2	0	1	1
40.33	40.34	2.235	0	6	1	3	3	4	76.62	76.62	1.2426	0	4	3	4	3	12
44.08	44.08	2.053	1	5	1	8	8	11	78.16	78.16	1.2220	1	1	3	6	5	19
44.34	44.34	2.041	0	8	0	16	16	23	79.44	79.44	1.2054	2	10	0	2	2	7
46.36	46.46	1.9568	0	0	2	26	36	40	80.23	80.24	1.1955	1	3	3	1	1	3
46.45		1.9535	1	7	0	22		33	80.85	80.90	1.1878	3	1	0	0	1	0
50.38	50.38	1.8100	0	8	1	8	8	14	80.91		1.1872	2	6	2	1		4
51.08	51.08	1.7865	2	0	0	19	17	32	81.08	81.14	1.1851	1	13	0	0	1	1
51.77	51.76	1.7646	0	4	2	3	3	5	81.81	81.80	1.1764	0	6	3	0	0	1
52.30	52.30	1.7478	1	7	1	22	20	39	82.92	82.92	1.1635	3	3	0	3	2	9
53.65	53.66	1.7069	1	1	2	2	2	3	83.93	83.94	1.1520	2	10	1	0	0	1
56.15	56.14	1.6368	1	3	2	19	19	37	84.35	84.34	1.1473	1	5	3	1	1	3
56.15		1.6367	2	4	0	2		4	85.33	85.32	1.1366	3	1	1	5	4	17
56.29	56.30	1.6331	0	10	0	4	15	8	85.55	85.58	1.1343	1	13	1	1	3	3
56.86		1.6179	1	9	0	0		0	86.63	86.64	1.1228	1	11	2	1	1	5
57.80	57.80	1.5939	2	2	1	1	2	3	87.01	87.14	1.1189	3	5	0	1	3	3
58.00	58.00	1.5888	0	6	2	2	2	4	87.11		1.1179	0	14	1	2		8
60.93	60.94	1.5193	1	5	2	5	5	11	87.17		1.1173	0	12	2	2		7
61.35	61.34	1.5100	2	4	1	17	15	37	87.37	87.38	1.1152	3	3	1	1	2	3
61.47		1.5072	0	10	1	0		1	88.08	88.08	1.1081	2	8	2	5	4	19
62.02	62.08	1.4952	1	9	1	1	2	3	88.97	88.98	1.0993	0	8	3	1	1	5
62.10		1.4935	2	6	0	1		3									
66.09	66.10	1.4126	0	8	2	7	6	18									
67.01	67.02	1.3954	2	6	1	1	1	3									
67.72	67.72	1.3825	1	7	2	11	9	29									
68.37	68.36	1.3710	1	11	0	1	1	4									

Table D.2. Simulated X-ray powder pattern for $\text{Sr}_{0.9}\text{Ca}_{0.1}\text{CuO}_2$

20	PEAK	d	h	k	l	l(INT)	l(PK)	l(DS)	20	PEAK	d	h	k	l	l(INT)	l(PK)	l(DS)
10.85	10.86	8.146	0	2	0	1	1	0	70.30	70.30	1.3379	2	8	0	6	5	16
21.80	21.82	4.073	0	4	0	16	18	9	71.82	71.82	1.3133	2	0	2	10	9	29
25.27	25.28	3.522	0	2	1	6	7	4	73.32	73.32	1.2901	1	11	1	12	10	35
25.67	25.68	3.468	1	1	0	18	20	12	73.63	73.54	1.2855	0	2	3	0	6	1
30.05	30.06	2.971	1	3	0	62	65	52	73.84	73.84	1.2824	0	12	1	1	1	2
31.72	31.72	2.819	0	4	1	56	58	50	74.98	74.98	1.2657	2	8	1	4	4	12
32.96	32.96	2.715	0	6	0	5	5	5	76.01	76.02	1.2510	0	10	2	3	3	8
34.56	34.56	2.593	1	1	1	100	100	100	76.09		1.2499	2	4	2	1		4
37.44	37.44	2.400	1	5	0	11	12	13	76.56	76.80	1.2434	1	9	2	0	3	0
38.02	38.02	2.365	1	3	1	12	12	14	76.81		1.2400	0	4	3	4		12
40.43	40.44	2.229	0	6	1	4	4	5	78.40	78.40	1.2188	1	1	3	6	5	19
44.26	44.26	2.045	1	5	1	7	8	9	79.86	79.86	1.2001	2	10	0	2	2	7
44.45	44.46	2.036	0	8	0	17	17	24	80.48	80.48	1.1924	1	3	3	1	1	4
46.47	46.48	1.9527	0	0	2	27	28	40	81.32	81.32	1.1823	2	6	2	1	1	4
46.63	46.62	1.9463	1	7	0	23	33	34	81.36		1.1817	1	13	0	0		0
50.50	50.50	1.8057	0	8	1	8	8	13	81.51	81.56	1.1800	3	1	0	0	1	0
51.45	51.46	1.7746	2	0	0	19	17	32	82.02	82.02	1.1739	0	6	3	0	0	1
51.88	51.88	1.7608	0	4	2	3	3	5	83.58	83.58	1.1560	3	3	0	2	2	9
52.49	52.50	1.7419	1	7	1	22	19	38	84.36	84.36	1.1472	2	10	1	0	0	1
53.84	53.84	1.7015	1	1	2	2	2	4	84.62	84.62	1.1443	1	5	3	1	1	2
56.33	56.34	1.6218	1	3	2	18	18	36	85.85	86.00	1.1311	1	13	1	1	4	2
56.43		1.6292	0	10	0	4		8	85.99		1.1295	3	1	1	4		16
56.52	56.48	1.6269	2	4	0	2	14	4	86.93	86.92	1.1198	1	11	2	1	1	5
58.14	58.16	1.5853	0	6	2	2	2	3	87.37	87.40	1.1152	0	14	1	2	3	8
58.16		1.5848	2	2	1	1		2	87.42		1.1147	0	12	2	2		7
61.13	61.14	1.5148	1	5	2	5	4	11	87.69	87.68	1.1120	3	5	0	1	2	3
61.63	61.72	1.5036	0	10	1	0	15	0	88.05	88.04	1.1084	3	3	1	1	1	3
61.72		1.5018	2	4	1	16		37	88.52	88.52	1.1037	2	8	2	5	4	20
62.24	62.24	1.4905	1	9	1	1	2	3	89.22	89.22	1.0969	0	8	3	1	1	5
62.47	62.46	1.4855	2	6	0	1	2	3									
66.26	66.26	1.4095	0	8	2	7	6	18									
67.39	67.40	1.3884	2	6	1	1	1	3									
67.95	67.94	1.3785	1	7	2	11	10	29									
68.60	68.60	1.3668	1	11	0	1	1	4									
69.13	69.14	1.3577	0	12	0	2	2	5									

Table D.3. Simulated X-ray powder pattern for $\text{Sr}_{0.8}\text{Ca}_{0.2}\text{CuO}_2$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
10.88	10.88	8.126	0	2	0	2	3	1	70.70	70.70	1.3314	2	8	0	6	5	16
21.86	21.86	4.063	0	4	0	16	18	9	72.21	72.20	1.3072	2	0	2	11	9	30
25.32	25.34	3.514	0	2	1	5	6	3	73.57	73.58	1.2863	1	11	1	12	10	35
25.84	25.84	3.445	1	1	0	21	23	15	73.81	73.78	1.2828	0	2	3	0	6	1
30.22	30.22	2.955	1	3	0	61	63	51	74.04	74.02	1.2793	0	12	1	1	1	2
31.79	31.80	2.813	0	4	1	56	59	51	75.38	75.38	1.2599	2	8	1	4	3	12
33.04	33.04	2.709	0	6	0	4	5	4	76.22	76.22	1.2481	0	10	2	3	2	8
34.73	34.74	2.581	1	1	1	100	100	100	76.49	76.46	1.2444	2	4	2	1	2	4
37.61	37.62	2.390	1	5	0	11	12	13	77.00	77.00	1.2374	0	4	3	4	4	12
38.19	38.20	2.355	1	3	1	13	13	15	78.65	78.64	1.2156	1	1	3	6	5	19
40.52	40.52	2.224	0	6	1	4	4	5	80.28	80.28	1.1949	2	10	0	2	2	7
44.43	44.56	2.037	1	5	1	6	20	8	80.74	80.74	1.1893	1	3	3	1	1	4
44.56		2.032	0	8	0	18		25	81.65	81.74	1.1783	1	13	0	0	1	0
46.57	46.58	1.9487	0	0	2	28	27	41	81.73		1.1773	2	6	2	1		3
46.81	46.82	1.9390	1	7	0	23	26	35	82.18	82.22	1.1721	3	1	0	0	0	1
50.63	50.64	1.8015	0	8	1	8	7	13	82.24		1.1714	0	6	3	0		1
51.83	51.82	1.7627	2	0	0	19	18	32	84.25	84.24	1.1484	3	3	0	2	2	8
52.00	51.96	1.7571	0	4	2	3	13	4	84.80	84.88	1.1424	2	10	1	0	1	1
52.68	52.68	1.7360	1	7	1	21	20	38	84.89		1.1414	1	5	3	1		2
54.02	54.02	1.6962	1	1	2	3	3	5	86.15	86.16	1.1279	1	13	1	1	1	2
56.53	56.54	1.6268	1	3	2	18	18	35	86.67	86.68	1.1224	3	1	1	4	4	16
56.58		1.6252	0	10	0	4		8	87.23	87.22	1.1167	1	11	2	1	1	5
56.89	56.88	1.6171	2	4	0	2	3	4	87.63	87.66	1.1126	0	14	1	2	3	8
58.28	58.28	1.5819	0	6	2	1	1	3	87.68		1.1121	0	12	2	2		7
58.54	58.52	1.5756	2	2	1	1	1	2	88.38	88.38	1.1051	3	5	0	1	1	3
61.34	61.34	1.5102	1	5	2	5	4	11	88.73	88.74	1.1016	3	3	1	1	1	3
61.80	62.10	1.5000	0	10	1	0	15	0	88.97	88.96	1.0993	2	8	2	5	5	20
62.09		1.4936	2	4	1	16		37	89.47	89.46	1.0945	0	8	3	1	1	5
62.45	62.26	1.4858	1	9	1	1	9	3									
62.85	62.84	1.4774	2	6	0	1	1	2									
66.42	66.42	1.4063	0	8	2	8	7	19									
67.78	67.78	1.3815	2	6	1	1	2	4									
68.17	68.18	1.3745	1	7	2	12	10	30									
68.85	68.84	1.3627	1	11	0	1	1	3									
69.33	69.32	1.3544	0	12	0	2	2	5									

Table D.4. Simulated X-ray powder pattern for $\text{Sr}_{0.7}\text{Ca}_{0.3}\text{CuO}_2$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
10.91	10.92	8.106	0	2	0	4	5	1	71.10	71.10	1.3249	2	8	0	6	5	17
21.91	21.92	4.053	0	4	0	15	17	9	72.60	72.60	1.3011	2	0	2	11	9	30
25.38	25.38	3.507	0	2	1	4	4	2	73.83	73.84	1.2825	1	11	1	12	10	35
26.01	26.02	3.423	1	1	0	25	27	17	73.99	74.04	1.2801	0	2	3	0	6	1
30.39	30.40	2.939	1	3	0	60	62	50	74.25		1.2763	0	12	1	1		2
31.86	31.86	2.806	0	4	1	57	57	51	75.79	75.80	1.2541	2	8	1	4	3	11
33.13	33.14	2.702	0	6	0	4	4	3	76.43	76.42	1.2453	0	10	2	3	2	8
34.89	34.90	2.569	1	1	1	100	100	100	76.89	76.90	1.2389	2	4	2	1	1	4
37.78	37.78	2.379	1	5	0	11	11	13	77.19	77.20	1.2348	0	4	3	4	4	12
38.36	38.36	2.345	1	3	1	14	14	16	78.90	78.90	1.2124	1	1	3	6	5	18
40.62	40.62	2.219	0	6	1	4	4	5	80.71	80.72	1.1896	2	10	0	2	2	7
44.61	44.68	2.030	1	5	1	5	21	7	81.00	80.98	1.1861	1	3	3	1	2	4
44.68		2.027	0	8	0	18		26	82.15	82.16	1.1723	2	6	2	1	1	3
46.67	46.68	1.9446	0	0	2	28	27	42	82.45	82.42	1.1689	0	6	3	0	1	1
47.00	47.00	1.9318	1	7	0	24	24	36	82.85	82.84	1.1642	3	1	0	0	0	1
48.08	48.08	1.8910	0	2	2	0	0	0	84.93	84.94	1.1409	3	3	0	2	2	8
50.76	50.76	1.7972	0	8	1	8	7	13	85.17	85.18	1.1384	1	5	3	0	1	2
52.12	52.20	1.7533	0	4	2	2	19	4	85.24		1.1376	2	10	1	0		0
52.20		1.7508	2	0	0	19		33	86.46	86.46	1.1247	1	13	1	0	0	2
52.88	52.88	1.7301	1	7	1	21	19	37	87.37	87.36	1.1153	3	1	1	4	4	16
54.21	54.20	1.6908	1	1	2	3	3	6	87.53	87.54	1.1136	1	11	2	1	2	4
56.72	56.72	1.6217	1	3	2	18	19	34	87.90	87.92	1.1099	0	14	1	2	3	8
56.73		1.6213	0	10	0	4		8	87.93		1.1096	0	12	2	2		6
57.27	57.28	1.6073	2	4	0	2	2	3	89.08	89.08	1.0982	3	5	0	1	1	3
58.42	58.42	1.5784	0	6	2	1	1	2	89.42	89.42	1.0949	2	8	2	5	5	21
58.91	58.92	1.5664	2	2	1	1	1	1	89.44		1.0948	3	3	1	1		4
61.54	61.54	1.5057	1	5	2	5	4	11	89.72	89.70	1.0921	0	8	3	1	4	4
62.47	62.48	1.4854	2	4	1	16	14	36									
62.67	62.64	1.4812	1	9	1	2	9	4									
63.24	63.24	1.4693	2	6	0	1	1	2									
66.59	66.60	1.4031	0	8	2	8	7	20									
68.17	68.18	1.3745	2	6	1	2	2	4									
68.40	68.40	1.3705	1	7	2	12	11	30									
69.09	69.08	1.3585	1	11	0	1	1	3									
69.52	69.52	1.3511	0	12	0	2	2	5									

Table D.5. Simulated X-ray powder pattern for $\text{Sr}_{0.6}\text{Ca}_{0.4}\text{CuO}_2$

20	PEAK	d	h	k	l	l(INT)	l(PK)	l(DS)	20	PEAK	d	h	k	l	l(INT)	l(PK)	l(DS)
10.93	10.94	8.087	0	2	0	6	8	2	69.71	69.72	1.3478	0	12	0	2	2	4
21.97	21.98	4.043	0	4	0	15	17	9	71.51	71.50	1.3183	2	8	0	6	5	17
25.44	25.44	3.499	0	2	1	2	3	2	73.00	73.00	1.2950	2	0	2	11	9	30
26.19	26.20	3.400	1	1	0	30	32	21	74.09	74.08	1.2787	1	11	1	12	10	35
30.56	30.58	2.922	1	3	0	58	59	49	74.17		1.2775	0	2	3	0		0
31.94	31.94	2.800	0	4	1	57	58	51	74.46	74.30	1.2732	0	12	1	1	6	2
33.21	33.22	2.696	0	6	0	3	3	3	76.21	76.20	1.2483	2	8	1	4	3	11
35.06	35.06	2.557	1	1	1	100	100	100	76.63	76.64	1.2424	0	10	2	3	3	8
37.96	37.96	2.369	1	5	0	11	11	13	77.30	77.38	1.2333	2	4	2	1	4	4
38.53	38.54	2.335	1	3	1	15	15	17	77.39		1.2322	0	4	3	4		12
40.72	40.72	2.214	0	6	1	5	5	6	79.15	79.14	1.2091	1	1	3	6	5	18
44.79	44.80	2.022	1	5	1	4	22	6	81.15	81.16	1.1843	2	10	0	2	2	7
44.79		2.022	0	8	0	19		27	81.26	81.24	1.1830	1	3	3	1	2	5
46.77	46.78	1.9406	0	0	2	29	28	43	82.58	82.60	1.1673	2	6	2	1	1	2
47.19	47.20	1.9245	1	7	0	25	24	37	82.67		1.1663	0	6	3	0		1
48.19	48.18	1.8870	0	2	2	0	0	0	83.55	83.54	1.1563	3	1	0	0	0	1
50.89	50.88	1.7930	0	8	1	7	7	12	85.45	85.64	1.1354	1	5	3	0	2	1
52.25	52.26	1.7495	0	4	2	2	3	4	85.63		1.1334	3	3	0	2		8
52.59	52.60	1.7389	2	0	0	19	18	33	86.77	86.76	1.1214	1	13	1	0	0	1
53.07	53.08	1.7242	1	7	1	21	19	36	87.83	87.84	1.1106	1	11	2	1	1	4
53.89	53.88	1.7000	2	2	0	0	0	0	88.07	88.08	1.1082	3	1	1	4	5	15
54.39	54.40	1.6854	1	1	2	4	4	8	88.17		1.1072	0	14	1	2		8
56.88	56.90	1.6173	0	10	0	4	18	8	88.19		1.1070	0	12	2	2		6
56.91		1.6166	1	3	2	17		33	89.80	89.88	1.0913	3	5	0	1	5	3
57.66	57.66	1.5974	2	4	0	2	2	3	89.88		1.0905	2	8	2	6		21
58.56	58.56	1.5749	0	6	2	1	1	2	89.97		1.0897	0	8	3	1		4
59.30	59.30	1.5572	2	2	1	0	0	1									
61.75	61.76	1.5011	1	5	2	5	4	11									
62.86	62.86	1.4772	2	4	1	16	15	36									
62.89		1.4765	1	9	1	2		4									
63.63	63.62	1.4612	2	6	0	1	1	2									
66.76	66.76	1.4000	0	8	2	8	7	20									
68.57	68.62	1.3675	2	6	1	2	11	4									
68.63		1.3665	1	7	2	12		31									
69.33	69.34	1.3543	1	11	0	1	1	3									

Table D.6. Simulated X-ray powder pattern for $\text{Sr}_{0.5}\text{Ca}_{0.5}\text{CuO}_2$

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
10.96	10.96	8.067	0	2	0	10	12	3	63.25		1.4690	2	4	1	16		35
22.02	22.02	4.034	0	4	0	15	16	9	64.02	64.02	1.4531	2	6	0	1	1	1
25.49	25.50	3.491	0	2	1	1	2	1	66.94	66.94	1.3968	0	8	2	9	8	21
26.37	26.38	3.377	1	1	0	35	37	25	68.86	68.86	1.3624	1	7	2	13	11	32
30.74	30.74	2.906	1	3	0	57	59	48	68.97		1.3605	2	6	1	2		4
32.01	32.02	2.794	0	4	1	57	59	51	69.58	69.58	1.3500	1	11	0	1	1	3
33.29	33.30	2.689	0	6	0	3	3	2	69.91	69.90	1.3445	0	12	0	2	2	4
35.23	35.24	2.546	1	1	1	100	100	100	71.92	71.92	1.3118	2	8	0	7	6	17
38.14	38.14	2.358	1	5	0	11	11	12	73.40	73.40	1.2889	2	0	2	11	9	30
38.70	38.70	2.325	1	3	1	17	16	19	74.35	74.34	1.2748	1	11	1	12	10	35
40.82	40.82	2.209	0	6	1	5	5	6	74.49		1.2728	2	2	2	0		0
44.91	44.92	2.017	0	8	0	20	21	28	74.67	74.56	1.2701	0	12	1	1	6	2
44.97		2.014	1	5	1	3		5	76.63	76.64	1.2424	2	8	1	3	3	10
46.88	46.88	1.9365	0	0	2	30	29	44	76.84	76.84	1.2396	0	10	2	3	4	8
47.38	47.38	1.9172	1	7	0	26	25	38	77.58	77.58	1.2296	0	4	3	4	4	12
48.29	48.30	1.8830	0	2	2	0	1	1	77.72	77.72	1.2277	2	4	2	1	2	3
51.02	51.02	1.7888	0	8	1	7	7	11	79.40	79.40	1.2059	1	1	3	6	5	18
52.37	52.38	1.7457	0	4	2	2	2	4	81.52	81.58	1.1798	1	3	3	2	3	5
52.98	52.98	1.7270	2	0	0	19	19	33	81.59		1.1790	2	10	0	2		7
53.27	53.28	1.7182	1	7	1	21	20	36	82.89	82.90	1.1638	0	6	3	0	0	1
54.28	54.28	1.6887	2	2	0	0	1	0	83.02	83.02	1.1623	2	6	2	0	1	2
54.58	54.58	1.6800	1	1	2	5	5	9	84.25	84.26	1.1484	3	1	0	0	0	1
57.04	57.10	1.6134	0	10	0	4	17	8	85.73	85.72	1.1324	1	5	3	0	0	1
57.11		1.6115	1	3	2	17		32	86.35	86.34	1.1258	3	3	0	2	2	7
57.91	58.06	1.5911	1	9	0	0	2	0	87.08	87.08	1.1182	1	13	1	0	0	1
58.05		1.5876	2	4	0	2		3	88.14	88.14	1.1075	1	11	2	1	1	4
58.71	58.70	1.5714	0	6	2	1	1	1	88.43	88.44	1.1046	0	14	1	2	4	8
59.68	59.68	1.5480	2	2	1	0	0	1	88.45		1.1044	0	12	2	2		6
61.96	61.96	1.4965	1	5	2	5	4	10	88.79	88.78	1.1010	3	1	1	4	4	15
63.12	63.26	1.4718	1	9	1	2	15	4									

Table D.7. Simulated X-ray powder pattern for $\text{Sr}_{0.4}\text{Ca}_{0.6}\text{CuO}_2$

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)	2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
10.99	11.00	8.047	0	2	0	14	17	5	63.65	63.66	1.4607	2	4	1	16	14	35
22.07	22.08	4.024	0	4	0	14	16	8	64.43	64.42	1.4450	2	6	0	0	0	1
25.55	25.56	3.484	0	2	1	1	1	0	67.11	67.10	1.3937	0	8	2	9	8	22
26.55	26.56	3.355	1	1	0	41	44	29	69.09	69.10	1.3584	1	7	2	13	11	33
30.92	30.92	2.890	1	3	0	55	57	47	69.38	69.28	1.3535	2	6	1	2	7	5
32.09	32.10	2.787	0	4	1	57	59	51	69.83	69.84	1.3458	1	11	0	1	1	3
33.38	33.38	2.682	0	6	0	2	2	2	70.11	70.10	1.3412	0	12	0	2	2	4
35.40	35.40	2.534	1	1	1	100	100	100	72.34	72.34	1.3052	2	8	0	7	6	18
38.32	38.32	2.347	1	5	0	11	11	12	73.81	73.82	1.2827	2	0	2	11	9	30
38.88	38.88	2.314	1	3	1	18	18	20	74.61	74.62	1.2710	1	11	1	12	11	35
40.92	40.92	2.204	0	6	1	6	5	7	74.88	74.84	1.2671	0	12	1	1	6	2
45.03	45.02	2.012	0	8	0	22	21	30	74.90		1.2668	2	2	2	0		1
45.16	45.14	2.006	1	5	1	3	16	3	77.05	77.06	1.2367	0	10	2	3	5	8
46.98	46.98	1.9324	0	0	2	31	30	45	77.06		1.2366	2	8	1	3		9
47.57	47.58	1.9099	1	7	0	27	26	40	77.78	77.78	1.2269	0	4	3	4	4	12
48.40	48.40	1.8790	0	2	2	1	1	1	78.14	78.12	1.2221	2	4	2	1	1	3
51.15	51.14	1.7845	0	8	1	7	6	11	79.66	79.66	1.2027	1	1	3	6	5	17
52.49	52.50	1.7420	0	4	2	2	2	4	81.79	81.78	1.1767	1	3	3	2	2	5
53.38	53.48	1.7151	2	0	0	19	29	34	82.04	82.04	1.1736	2	10	0	2	3	7
53.47		1.7122	1	7	1	20		35	83.11	83.10	1.1613	0	6	3	0	0	2
54.67	54.78	1.6774	2	2	0	0	6	1	83.46	83.46	1.1572	2	6	2	0	0	1
54.78		1.6745	1	1	2	6		11	84.97	84.96	1.1405	3	1	0	0	0	1
57.19	57.32	1.6095	0	10	0	5	17	9	86.01	86.02	1.1294	1	5	3	0	0	1
57.31		1.6064	1	3	2	16		31	87.07	87.08	1.1183	3	3	0	2	2	7
58.13	58.12	1.5857	1	9	0	0	1	1	87.40	87.34	1.1150	1	13	1	0	1	1
58.45	58.44	1.5777	2	4	0	1	1	3	88.45	88.46	1.1044	1	11	2	1	1	4
58.85	58.84	1.5679	0	6	2	0	1	1	88.70	88.72	1.1019	0	14	1	2	3	7
60.08	60.08	1.5387	2	2	1	0	0	0	88.71		1.1018	0	12	2	1		5
62.17	62.18	1.4919	1	5	2	5	4	10	89.53	89.52	1.0939	3	1	1	4	3	14
63.35	63.36	1.4670	1	9	1	2	2	5									

Table D.8. Simulated X-ray powder pattern for $\text{Sr}_{0.3}\text{Ca}_{0.7}\text{CuO}_2$

2θ	PEAK	d	h	k	l	(INTI(PK)) (DS)				2θ	PEAK	d	h	k	l	(INTI(PK)) (DS)			
11.01	11.02	8.028	0	2	0	20	25	7		64.84	64.84	1.4368	2	6	0	0	0	1	
22.13	22.14	4.014	0	4	0	14	15	8		67.28	67.28	1.3905	0	8	2	10	8	23	
25.60	25.62	3.476	0	2	1	0	0	0		69.33	69.32	1.3543	1	7	2	14	11	34	
26.73	26.74	3.332	1	1	0	48	52	35		69.79	69.80	1.3464	2	6	1	2	2	5	
31.10	31.10	2.874	1	3	0	54	55	46		70.08	70.08	1.3416	1	11	0	1	2	3	
32.16	32.16	2.781	0	4	1	58	59	51		70.30	70.30	1.3379	0	12	0	1	2	4	
33.46	33.46	2.676	0	6	0	1	2	1		72.77	72.76	1.2986	2	8	0	7	6	19	
35.58	35.58	2.521	1	1	1	100	100	100		74.23	74.24	1.2766	2	0	2	11	9	30	
38.50	38.50	2.337	1	5	0	11	11	12		74.88	74.88	1.2671	1	11	1	13	11	35	
39.06	39.06	2.304	1	3	1	20	20	22		75.09	75.10	1.2640	0	12	1	1	7	3	
41.02	41.02	2.199	0	6	1	6	6	7		75.32		1.2607	2	2	2	0		1	
45.14	45.14	2.007	0	8	0	23	22	31		77.26	77.26	1.2338	0	10	2	3	3	9	
45.34	45.24	1.9984	1	5	1	2	15	2		77.50	77.50	1.2307	2	8	1	3	4	8	
47.09	47.10	1.9284	0	0	2	32	30	47		77.98	77.98	1.2243	0	4	3	4	4	12	
47.77	47.78	1.9025	1	7	0	28	26	41		78.13	78.20	1.2223	1	9	2	0	2	1	
48.51	48.52	1.8750	0	2	2	1	1	1		78.57	78.58	1.2165	2	4	2	1	1	3	
51.28	51.28	1.7803	0	8	1	6	6	10		79.92	79.92	1.1994	1	1	3	6	5	17	
52.61	52.62	1.7382	0	4	2	2	2	4		82.05	82.06	1.1735	1	3	3	2	2	6	
53.68	53.68	1.7062	1	7	1	20	23	34		82.50	82.50	1.1683	2	10	0	2	2	7	
53.78	53.78	1.7032	2	0	0	20	28	34		83.33	83.32	1.1588	0	6	3	1	0	2	
54.97	54.98	1.6690	1	1	2	8	7	13		83.91	83.92	1.1522	2	6	2	0	0	1	
55.08		1.6661	2	2	0	1		1		85.70	85.70	1.1326	3	1	0	1	0	2	
57.34	57.36	1.6055	0	10	0	5	6	9		86.30	86.30	1.1264	1	5	3	0	0	0	
57.51	57.50	1.6013	1	3	2	16	16	30		87.71	87.82	1.1118	1	13	1	0	2	0	
58.34	58.34	1.5803	1	9	0	1	1	1		87.82		1.1107	3	3	0	2		7	
58.85	58.86	1.5679	2	4	0	1	1	3		88.77	88.78	1.1013	1	11	2	1	1	4	
58.99	59.00	1.5645	0	6	2	0	1	1		88.97	88.98	1.0993	0	12	2	1	3	5	
62.39	62.38	1.4873	1	5	2	5	4	10		88.98		1.0992	0	14	1	2		7	
63.57	63.58	1.4623	1	9	1	2	2	5											
64.06	64.06	1.4524	2	4	1	16	14	35											

Table D.9. Simulated X-ray powder pattern for $\text{Sr}_{0.25}\text{Ca}_{0.75}\text{CuO}_2$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
11.03	11.04	8.018	0	2	0	23	29	8	65.05	65.04	1.4327	2	6	0	0	0	0
22.16	22.16	4.009	0	4	0	14	15	8	67.37	67.36	1.3889	0	8	2	10	9	23
26.82	26.84	3.321	1	1	0	53	57	38	69.45	69.44	1.3523	1	7	2	14	12	34
31.19	31.20	2.865	1	3	0	53	55	45	70.00	70.00	1.3429	2	6	1	2	2	5
32.20	32.20	2.778	0	4	1	58	60	51	70.21	70.20	1.3395	1	11	0	1	2	3
33.50	33.50	2.673	0	6	0	1	1	1	70.40	70.40	1.3363	0	12	0	1	2	4
35.66	35.66	2.515	1	1	1	100	100	100	72.98	72.98	1.2953	2	8	0	7	6	19
38.59	38.60	2.331	1	5	0	11	11	12	74.44	74.44	1.2735	2	0	2	11	10	30
39.15	39.16	2.299	1	3	1	21	21	23	75.01	75.02	1.2652	1	11	1	13	11	34
41.07	41.08	2.196	0	6	1	6	6	8	75.20	75.22	1.2625	0	12	1	1	7	3
45.20	45.20	2.004	0	8	0	24	23	32	75.54		1.2577	2	2	2	0		1
45.44	45.30	1.9945	1	5	1	1	15	2	77.37	77.36	1.2324	0	10	2	3	3	9
47.14	47.14	1.9263	0	0	2	33	32	47	77.72	77.72	1.2277	2	8	1	3	3	8
47.87	47.86	1.8988	1	7	0	29	27	42	78.08	78.08	1.2230	0	4	3	4	4	12
48.57	48.56	1.8730	0	2	2	1	1	2	78.27	78.30	1.2205	1	9	2	0	2	1
51.34	51.34	1.7782	0	8	1	6	6	10	78.79	78.80	1.2137	2	4	2	1	1	3
52.67	52.68	1.7363	0	4	2	2	2	3	80.05	80.04	1.1978	1	1	3	6	5	17
53.78	53.78	1.7032	1	7	1	20	20	34	82.19	82.18	1.1719	1	3	3	2	2	6
53.98	53.98	1.6973	2	0	0	20	24	34	82.73	82.74	1.1656	2	10	0	2	2	7
55.07	55.08	1.6663	1	1	2	8	8	15	83.44	83.44	1.1575	0	6	3	1	1	2
55.28	55.22	1.6605	2	2	0	1	5	1	84.14	84.14	1.1496	2	6	2	0	0	1
57.42	57.42	1.6035	0	10	0	5	6	9	86.07	86.08	1.1287	3	1	0	1	0	2
57.61	57.60	1.5987	1	3	2	16	16	29	87.87	87.88	1.1101	1	13	1	0	0	0
58.45	58.46	1.5776	1	9	0	1	1	2	88.19	88.20	1.1070	3	3	0	2	2	6
59.06	59.06	1.5629	2	4	0	1	1	3	88.92	88.94	1.0997	1	11	2	1	1	4
59.07		1.5627	0	6	2	0		0	89.11	89.12	1.0980	0	12	2	1	3	5
62.49	62.50	1.4850	1	5	2	5	4	10	89.11		1.0979	0	14	1	2		7
62.71	62.66	1.4804	0	10	1	0	3	0									
63.69	63.70	1.4599	1	9	1	2	2	5									
64.26	64.26	1.4483	2	4	1	16	14	34									

APPENDIX E: $\text{Ca}_{0.14}\text{Sr}_{0.86}\text{CuO}_2$

Table E.1. Simulated X-ray powder pattern for $\text{Ca}_{0.14}\text{Sr}_{0.86}\text{CuO}_2$

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
23.02	23.02	3.861	1	0	0	2	2	1
27.86	27.88	3.200	0	0	1	11	11	8
32.78	32.78	2.730	1	1	0	31	32	27
36.44	36.44	2.464	1	0	1	100	100	100
43.54	43.54	2.077	1	1	1	1	1	2
47.03	47.04	1.9305	2	0	0	37	34	51
52.99	52.98	1.7267	2	1	0	1	0	1
55.55	55.56	1.6530	2	0	1	4	3	7
57.57	57.58	1.5998	0	0	2	9	8	16
60.92	60.92	1.5196	2	1	1	37	33	75

20	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
62.83	62.82	1.4779	1	0	2	0	0	1
67.85	67.84	1.3803	1	1	2	8	7	18
68.70	68.70	1.3651	2	2	0	9	8	22
75.69	75.68	1.2556	2	2	1	1	1	3
77.42	77.42	1.2318	2	0	2	12	10	34
78.23	78.24	1.2210	3	1	0	5	4	14
80.35	80.34	1.1940	3	0	1	7	6	22
82.05	82.06	1.1735	2	1	2	0	0	1
84.95	84.94	1.1407	3	1	1	0	0	0

APPENDIX F: $(\text{Ca,Sr})\text{Cu}_2\text{O}_3$

Table F.1. Simulated X-ray powder pattern for CaCu_2O_3 Model 1

20	PEAK	d	h	k	l	INT	PK	DS	20	PEAK	d	h	k	l	INT	PK	DS
17.83	17.84	4.971	2	0	0	6	7	3	66.59	66.60	1.4032	6	1	1	13	11	27
23.56	23.56	3.773	1	1	0	6	7	4	69.76	70.14	1.3470	1	3	0	0	6	0
25.73	25.74	3.459	0	0	1	16	17	10	70.10		1.3413	7	1	0	0	0	
27.28	27.28	3.267	1	0	1	22	23	15	70.13		1.3407	4	1	2	7	15	
31.48	31.40	2.839	2	0	1	62	63	51	71.46	71.46	1.3190	0	2	2	1	1	2
33.96	33.96	2.638	0	1	1	88	91	79	71.62	71.64	1.3165	5	2	1	1	1	2
34.85	34.86	2.572	3	1	0	72	74	66	71.79	71.80	1.3138	7	0	1	0	1	1
35.17	35.16	2.550	1	1	1	14	18	13	72.19	72.20	1.3076	1	2	2	6	5	13
36.11	36.12	2.486	4	0	0	1	1	1	72.36	72.38	1.3049	5	0	2	3	5	7
37.56	37.56	2.393	3	0	1	100	100	100	73.60	73.60	1.2860	6	2	0	11	9	26
38.61	38.60	2.330	2	1	1	0	1	0	74.34	74.34	1.2749	2	2	2	0	0	1
43.83	43.84	2.064	3	1	1	4	5	5	75.00	75.00	1.2653	0	3	1	4	3	9
44.39	44.38	2.039	0	2	0	54	52	67	75.53	75.52	1.2578	3	3	0	4	3	9
44.87	44.88	2.018	4	0	1	16	17	20	75.71	75.74	1.2552	1	3	1	1	2	2
48.19	48.20	1.8867	2	2	0	1	1	1	76.04	76.04	1.2506	7	1	1	1	1	2
51.06	51.06	1.7873	5	1	0	0	0	0	77.89	77.88	1.2255	3	2	2	4	3	11
52.01	52.02	1.7567	0	2	1	3	3	4	79.44	79.44	1.2054	6	2	1	1	1	2
52.88	52.90	1.7299	1	2	1	3	5	5	80.15	80.16	1.1965	6	0	2	1	0	1
52.90		1.7295	0	0	2	2	3		81.33	81.34	1.1821	3	3	1	0	0	1
53.08	53.04	1.7239	5	0	1	2	4	3	82.39	82.40	1.1696	8	0	1	1	1	3
53.75	53.76	1.7039	1	0	2	11	10	17	82.77	82.64	1.1651	4	2	2	0	1	1
55.40	55.42	1.6570	6	0	0	21	30	34	83.84	83.84	1.1530	0	0	3	1	1	2
55.43		1.6563	2	2	1	13	22		84.28	84.28	1.1481	6	1	2	0	0	1
56.27	56.28	1.6335	2	0	2	1	1	1	86.60	86.60	1.1232	2	0	3	2	1	5
57.86	57.88	1.5923	0	1	2	1	1	1	87.94	87.94	1.1095	0	1	3	0	0	0
58.04	58.04	1.5879	5	1	1	2	2	4	88.44	88.62	1.1045	7	2	1	0	1	1
58.50	58.50	1.5766	4	2	0	0	0	0	88.63		1.1027	1	1	3	2	5	
58.67	58.68	1.5722	1	1	2	0	1	1	88.98	88.98	1.0992	5	2	2	2	2	7
59.51	59.52	1.5521	3	2	1	31	27	56	89.14	89.14	1.0976	7	0	2	1	1	3
60.32	60.32	1.5333	3	0	2	8	7	14									
61.06	61.06	1.5164	2	1	2	11	10	21									
62.06	62.06	1.4944	6	0	1	1	1	2									
64.92	64.94	1.4352	3	1	2	4	8	7									
64.95		1.4346	4	2	1	6	12										
65.72	65.72	1.4196	4	0	2	0	0	1									

Table F.2. Simulated X-ray powder pattern for CaCu_2O_3 Model 2

2θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
17.83	17.84	4.971	2	0	0	6	6	3
23.56	23.56	3.773	1	1	0	4	4	2
25.73	25.74	3.459	0	0	1	12	14	8
27.28	27.28	3.267	1	0	1	22	24	16
31.48	31.48	2.839	2	0	1	58	59	47
33.96	33.96	2.638	0	1	1	73	75	65
34.85	34.86	2.572	3	1	0	69	72	64
35.17	35.16	2.550	1	1	1	17	21	15
36.11	36.12	2.486	4	0	0	1	1	0
37.56	37.56	2.393	3	0	1	100	100	100
43.83	43.84	2.064	3	1	1	8	8	10
44.39	44.38	2.039	0	2	0	53	50	65
44.87	44.88	2.018	4	0	1	15	15	18
48.19	48.20	1.8867	2	2	0	1	1	1
50.40	50.40	1.8090	4	1	1	0	0	1
51.06	51.06	1.7873	5	1	0	1	1	2
52.01	52.02	1.7567	0	2	1	2	2	4
52.88	52.90	1.7299	1	2	1	3	5	5
52.90		1.7295	0	0	2	2		3
53.08	53.04	1.7239	5	0	1	2	4	3
53.75	53.76	1.7039	1	0	2	10	9	16
55.40	55.42	1.6570	6	0	0	20	29	33
55.43		1.6563	2	2	1	13		21
56.27	56.28	1.6335	2	0	2	1	1	1
57.86	57.88	1.5923	0	1	2	1	1	2
58.04	58.04	1.5879	5	1	1	4	4	7
58.50	58.48	1.5766	4	2	0	0	0	0
59.51	59.52	1.5521	3	2	1	31	27	55
60.32	60.32	1.5333	3	0	2	7	7	14
61.06	61.06	1.5164	2	1	2	14	12	25
62.06	62.06	1.4944	6	0	1	1	1	2
64.92	64.94	1.4352	3	1	2	1	6	3
64.95		1.4346	4	2	1	6		11
65.72	65.72	1.4196	4	0	2	0	0	1
66.59	66.60	1.4032	6	1	1	11	10	23

Table F.3. Simulated X-ray powder pattern for CaCu_2O_3 Model 3

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
17.83	17.84	4.971	2	0	0	2	3	1	60.32	60.32	1.5333	3	0	2	5	5	10
23.56	23.56	3.773	1	1	0	4	4	2	61.06	61.06	1.5164	2	1	2	9	8	17
25.73	25.74	3.459	0	0	1	26	28	17	62.06	62.06	1.4944	6	0	1	2	1	3
27.28	27.28	3.267	1	0	1	5	5	3	64.92	64.94	1.4352	3	1	2	2	3	3
31.48	31.48	2.839	2	0	1	17	18	14	64.95		1.4346	4	2	1	3		5
33.96	33.96	2.638	0	1	1	39	40	35	65.72	65.72	1.4196	4	0	2	0	0	1
34.85	34.86	2.572	3	1	0	53	55	48	66.59	66.60	1.4032	6	1	1	7	6	14
35.17	35.18	2.550	1	1	1	34	37	31	70.13	70.14	1.3407	4	1	2	5	4	11
36.11	36.12	2.486	4	0	0	1	2	1	71.46	71.46	1.3190	0	2	2	1	1	2
37.56	37.56	2.393	3	0	1	100	100	100	71.62	71.66	1.3165	5	2	1	0	1	0
38.61	38.60	2.330	2	1	1	2	2	2	71.79		1.3138	7	0	1	0		0
43.83	43.84	2.064	3	1	1	0	1	0	72.19	72.20	1.3076	1	2	2	4	4	9
44.39	44.38	2.039	0	2	0	40	38	49	72.36	72.38	1.3049	5	0	2	2	3	4
44.87	44.88	2.018	4	0	1	6	7	7	73.60	73.60	1.2860	6	2	0	8	7	19
48.19	48.20	1.8867	2	2	0	0	0	0	74.34	74.34	1.2749	2	2	2	0	0	1
50.40	50.40	1.8090	4	1	1	0	0	1	75.00	75.00	1.2653	0	3	1	2	2	5
51.06	51.06	1.7873	5	1	0	0	0	1	75.53	75.54	1.2578	3	3	0	3	3	7
52.01	52.02	1.7567	0	2	1	4	3	6	75.71	75.74	1.2552	1	3	1	1	2	3
52.88	52.90	1.7299	1	2	1	1	3	1	76.04	76.04	1.2506	7	1	1	1	1	3
52.90		1.7295	0	0	2	2		3	77.89	77.88	1.2255	3	2	2	3	2	7
53.08	53.02	1.7239	5	0	1	0	2	0	79.44	79.44	1.2054	6	2	1	1	1	2
53.75	53.76	1.7039	1	0	2	8	7	12	80.15	80.16	1.1965	6	0	2	1	1	2
55.40	55.42	1.6570	6	0	0	15	17	25	82.39	82.40	1.1696	8	0	1	0	0	1
55.43		1.6563	2	2	1	5		7	82.77	82.76	1.1651	4	2	2	0	0	1
56.27	56.28	1.6335	2	0	2	1	1	1	83.84	83.84	1.1530	0	0	3	1	1	2
57.86	58.04	1.5923	0	1	2	1	5	1	84.28	84.28	1.1481	6	1	2	0	0	0
58.04		1.5879	5	1	1	5		9	86.60	86.60	1.1232	2	0	3	1	1	3
58.50	58.50	1.5766	4	2	0	0	1	1	88.63	88.62	1.1027	1	1	3	1	1	4
58.67	58.66	1.5722	1	1	2	0	1	0	88.98	88.98	1.0992	5	2	2	1	2	4
59.51	59.52	1.5521	3	2	1	30	26	53	89.14	89.14	1.0976	7	0	2	1	1	3

Table F.4. Simulated X-ray powder pattern for CaCu_2O_3 Model 4

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
17.83	17.84	4.971	2	0	0	4	4	2
23.56	23.56	3.773	1	1	0	4	5	3
25.73	25.74	3.459	0	0	1	29	32	19
27.28	27.28	3.267	1	0	1	4	4	3
31.48	31.48	2.839	2	0	1	20	20	16
33.96	33.96	2.638	0	1	1	42	44	38
34.85	34.86	2.572	3	1	0	54	56	49
35.17	35.18	2.550	1	1	1	34	37	31
36.11	36.12	2.486	4	0	0	1	1	1
37.56	37.56	2.393	3	0	1	100	100	100
38.61	38.60	2.330	2	1	1	1	2	2
43.83	44.38	2.064	3	1	1	0	39	0
44.39		2.039	0	2	0	41		50
44.87	44.88	2.018	4	0	1	6	7	8
48.19	48.20	1.8867	2	2	0	0	0	1
50.40	50.40	1.8090	4	1	1	1	1	1
51.06	51.06	1.7873	5	1	0	0	0	0
52.01	52.02	1.7567	0	2	1	4	4	6
52.88	52.90	1.7299	1	2	1	1	3	1
52.90		1.7295	0	0	2	2		3
53.08	53.04	1.7239	5	0	1	0	2	1
53.75	53.76	1.7039	1	0	2	8	7	13
55.40	55.42	1.6570	6	0	0	16	18	26
55.43		1.6563	2	2	1	5		8
56.27	56.28	1.6335	2	0	2	0	1	1
57.86	58.04	1.5923	0	1	2	0	4	1
58.04		1.5879	5	1	1	4		8
58.50	58.50	1.5766	4	2	0	0	1	0
58.67	58.66	1.5722	1	1	2	0	1	0
59.51	59.52	1.5521	3	2	1	30	26	54
60.32	60.32	1.5333	3	0	2	6	6	11
61.06	61.06	1.5164	2	1	2	9	8	17
62.06	62.06	1.4944	6	0	1	2	2	3
64.92	64.94	1.4352	3	1	2	2	4	4
64.95		1.4346	4	2	1	3		5

2θ	PEAK	d	h	k	l	I(NT)	I(PK)	I(DS)
65.72	65.72	1.4196	4	0	2	0	0	0
66.59	66.60	1.4032	6	1	1	7	6	15
70.10	70.14	1.3413	7	1	0	0	4	0
70.13		1.3407	4	1	2	5		11
71.46	71.46	1.3190	0	2	2	1	1	2
71.62	71.66	1.3165	5	2	1	0	1	0
71.79		1.3138	7	0	1	0		0
72.19	72.20	1.3076	1	2	2	4	4	10
72.36	72.38	1.3049	5	0	2	2	4	5
73.60	73.60	1.2860	6	2	0	8	7	20
74.34	74.34	1.2749	2	2	2	0	0	1
75.00	75.00	1.2653	0	3	1	2	2	5
75.53	75.54	1.2578	3	3	0	3	3	7
75.71	75.74	1.2552	1	3	1	1	2	3
76.04	76.04	1.2506	7	1	1	1	2	4
77.89	77.88	1.2255	3	2	2	3	3	8
79.44	79.44	1.2054	6	2	1	1	1	3
80.15	80.16	1.1965	6	0	2	1	0	1
82.39	82.40	1.1696	8	0	1	0	0	1
82.77	82.76	1.1651	4	2	2	0	0	0
83.84	83.84	1.1530	0	0	3	1	1	2
84.28	84.28	1.1481	6	1	2	0	0	0
86.60	86.60	1.1232	2	0	3	1	1	3
88.63	88.62	1.1027	1	1	3	1	1	5
88.98	88.98	1.0992	5	2	2	2	2	5
89.14	89.14	1.0976	7	0	2	1	1	3

APPENDIX G: (Ca,Sr)Cu₂O₂

Table G.1. Simulated X-ray powder pattern for SrCu_2O_2

2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)	2 θ	PEAK	d	h	k	l	I(INT)	I(PK)	I(DS)
18.55	18.56	4.779	1	0	1	19	21	11	61.84	61.84	1.4991	3	2	1	14	13	39
29.37	29.38	3.039	1	1	2	100	100	100	66.50	66.50	1.4050	2	0	6	7	6	21
31.82	31.82	2.810	1	0	3	52	51	57	68.06	68.08	1.3764	3	2	3	0	0	0
32.72	32.72	2.734	2	0	0	36	35	41	68.58	68.58	1.3672	4	0	0	11	9	36
37.62	37.62	2.389	2	0	2	50	51	68	70.39	70.38	1.3365	3	0	5	5	4	15
37.88	37.88	2.373	2	1	1	65	66	90	76.31	76.32	1.2469	3	3	2	3	3	13
46.29	46.30	1.9597	2	1	3	1	1	2	77.59	77.60	1.2294	4	1	3	7	6	25
49.23	49.24	1.8494	1	0	5	15	13	30	77.68		1.2283	0	0	8	4		13
49.86	49.86	1.8274	2	0	4	17	15	34	78.08	78.08	1.2229	4	2	0	3	3	12
50.90	50.90	1.7924	3	0	1	0	0	1	78.50	78.50	1.2175	2	1	7	6	5	25
56.35	56.36	1.6313	3	1	2	22	19	51	80.75	80.76	1.1891	3	1	6	6	5	23
57.84	57.84	1.5929	3	0	3	9	8	22	80.95	80.96	1.1867	4	2	2	7	7	26
60.37	60.40	1.5319	2	1	5	0	1	1	86.87	86.86	1.1204	2	0	8	2	2	10
60.93	60.92	1.5194	2	2	4	35	30	94	88.96	88.96	1.0994	4	1	5	4	3	20
61.43	61.44	1.5080	1	1	6	8	8	21	89.44	89.44	1.0948	4	2	4	4	3	20

INTERNAL DISTRIBUTION

1-2. Central Research Library	25. M. S. Lubell
3. Document Reference Section	26. B. W. McConnell
4-5. Laboratory Records Department	27. H. Payne
6. Laboratory Records, ORNL-RC	28-32. B. J. Reardon
7. ORNL Patent Section	33. J. B. Roberto
8-10. M&C Records Office	34. A. C. Schaffhauser
11. R. S. Carlsmith	35. E. J. Soderstrom
12. O. B. Cavin	36. E. D. Specht
13. D. K. Christen	37. V. J. Tennery
14. D. F. Craig	38. Z. L. Wang
15. L. B. Dunlap	39. Y. A. Chang (Consultant)
16. F. Foust	40. H. W. Foglesong (Consultant)
17. J. D. Griffin	41. J. J. Hren (Consultant)
18. R. A. Hawsey	42. M. L. Savitz (Consultant)
19-23. C. R. Hubbard	43. J. G. Simon (Consultant)
24. D. M. Kroeger	44. K. E. Spear (Consultant)

EXTERNAL DISTRIBUTION

45. ALFRED UNIVERSITY, Binns-Merill Hall, Alfred, NY 14802

R. L. Snyder

- 46-47. ARGONNE NATIONAL LABORATORY, 9700 S. Cass Avenue, Argonne, IL 60439

S. Lake (TTC/900)

R. Poeppel (Bldg 212)

48. BROOKHAVEN NATIONAL LABORATORY, Department of Applied Science, MTL Science Division, Building 480, Upton, Long Island, NY 11973

D. O. Welch

49. CORNING INCORPORATED, Research, Development & Engineering, Instrumental Analysis Department, SP FR OI 8, Corning, NY 14831

H. J. Holland

50. EASTMAN KODAK COMPANY, Kodak Park, Building 49, Rochester, NY 14652-3712

T. N. Blanton

51. ENERGETICS, INC., Project Manager, 7164 Columbia Gateway Drive,
Columbia, MD 21046

J. Badin

- 52-54. LOS ALAMOS NATIONAL LABORATORY, P. O. Box 1663, Los Alamos,
NM 87545

K. Adams (MS K763)
L. S. Blair, Industrial Program Manager (ERDC/SPC, MS K763)
E. Peterson (MS K763)

55. MONASH UNIVERSITY, Department of Physics, Clayton 3168, Australia

R. A. Coyle

- 56-58. NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY, Materials
Science & Engineering Laboratory, Gaithersburg, MD 20899

L. P. Cook
R. S. Roth
W. Wong-Ng

59. NATIONAL RENEWABLE ENERGY LABORATORY, 1617 Cole Blvd.,
Golden, CO 80401

R. D. Blaugher

60. NAVAL WEAPONS CENTER, Code 3851, China Lake, CA 93555

C. Lowe-Ma

61. SANDIA NATIONAL LABORATORIES, Division 6221, P. O. Box 5800,
Albuquerque, NM 87185

T. C. Bickel

62. U. S. DOE, ADVANCED UTILITY CONCEPTS DIVISION, Director, Forrestal
RM 5F064, MS CE142, 1000 Independence Avenue SW, Washington, DC 20585

R. Eaton

- 63-64. U. S. DOE, CONSERVATION AND RENEWABLE ENERGY, Forrestal
Building, 1000 Independence Avenue, S. W., Washington, DC 20585

A. A. Chesnes, Deputy Assistant Secretary
J. J. Eberhardt

65. U. S. DOE, SUPERCONDUCTIVITY SYSTEMS OFFICE OF ENERGY
MANAGEMENT, Program Manager, Forrestal RM 5F064, 1000
Independence Avenue SW, Washington, DC 20585

J. Daley (MS CE142)
- 66-69. U. S. DOE, OAK RIDGE FIELD OFFICE, P. O. Box 2008, Oak Ridge,
TN 37831-6269

Assistant Manager for Energy Research and Development
G. C. Manthey
G. L. Riner
M. J. Rohr
- 70-79. U. S. DOE, OFFICE OF SCIENTIFIC AND TECHNICAL INFORMATION,
P. O. Box 62, Oak Ridge, TN 37831

For distribution by microfiche as shown in DOE/OSTI-4500, Distribution
Category UC-364 (Superconducting Materials)

END

**DATE
FILMED**

7 / 23 / 92