Review of the Data Bases for Making Decisions Regarding Trojan Steam Generator Replacement Options

**A. B. Johnson, Jr.
E. R. Gilbert**

March 1992

**Prepared for
Bonneville Power Administration
under a Related Services Agreement
with the U.S. Department Energy
Contract DE-AC06-76RLO 1830**

**Pacific Northwest Laboratory
Operated for the U.S. Department of Energy
by Battelle Memorial Institute**

PNL-8038

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor Battelle Memorial Institute, nor any of their employees, makes **any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.** Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof, or Battelle Memorial Institute. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

PACIFIC NORTHWEST LABORATORY
operated by
BATTELLE MEMORIAL INSTITUTE
for the
UNITED STATES DEPARTMENT OF ENERGY
under Contract DE-AC06-76RLO 1830

Printed in the United States of America

Available to DOE and DOE contractors from the
Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831;
prices available from (615) 576-8401. FTS 626-8401.

Available to the public from the National Technical Information Service,
U.S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

PNL--8038

DE92 011377

REVIEW OF THE DATA BASES FOR MAKING
DECISIONS REGARDING TROJAN STEAM
GENERATOR REPLACEMENT OPTIONS

A. B. Johnson, Jr.
E. R. Gilbert

March 1992

Prepared for
Bonneville Power Administration
under a Related Services Agreement
with the U.S. Department of Energy
under Contract DE-AC06-76RLO 1830

Pacific Northwest Laboratory
Richland, Washington 99352

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

SUMMARY

The central focus for this assessment has been to compare the corrosion behavior of two SG tube materials: Inconel 600 TT and Inconel 690 TT from a) SG operating experience, and b) laboratory data. The scope and results of the comparisons are summarized in this section. They provide the basis for projecting SG longevity.

SCOPE AND RESULTS BASED ON REACTOR SERVICE

Due to the complex nature of SG design and operation, it is not valid to fully isolate material behavior as a variable. Rather, we present an integrated perspective that includes SG design, operation, and materials. Isolation of materials comparisons is addressed in the laboratory studies (Sections 4 and 6.2).

Alloy 600 TT

The data base focuses on thermally-treated Inconel 600 in U.S. reactors fabricated by Westinghouse, to maintain relevance to the Seabrook Unit 2 units that are under consideration. The fact that 49 SGs in U.S. reactors (about 80 worldwide) with a combined experience of 280 SG-years have operated for periods up to 11 years (through 1992), free of tube plugging due to corrosion (data through 1990) is substantial evidence that major advances have been made in controlling SG degradation. Higher integrity tube material is only one factor in the complex array of potential contributors that include improved water chemistry control, removal of copper sources, advancements in crevice design, and more corrosion-resistant tube support and tube sheet materials.

Based on reactor service experience we conclude that Alloy 600 TT is emerging as a satisfactory material for extended operation in SGs. There seems to have been little opportunity in recent service to evaluate how the material will behave in severe upset conditions, e.g., such as the brackish water ingress at Indian Point Unit 3. However, specific strengths and vulnerabilities are considered, based on laboratory results (Section 5).

Alloy 690 TT

The reactor service data base for Alloy 690 TT was summarized in Table 2: 11 SGs in service for about 30 SG-years, with a maximum service time of about three years. While the service experience has been positive (no tubes plugged for any cause), the experience, by itself, provides an insufficient basis for major conclusions.

LABORATORY RESULTS

Testing of Alloy 690 TT for periods of up to four years in primary coolant chemistry and up to eight years with secondary system chemistry consistently shows more resistance to cracking than similar testing of Alloy 600 MA or 600 TT. No detectable degradation has been found in most tests or during the steam generator reactor service. Extrapolations with limited validity imply that the margin of performance improvement provided by Alloy 600 TT over Alloy 600 MA in SGs is at least twice the service longevity. The use of Alloy 690 TT over Alloy 600 TT should provide an unbounded improvement on the primary side, but perhaps only an additional improvement of a few years for the secondary side. However, it should be realized that the actual performance is affected by numerous factors and may not be realized unless the operating parameters of a steam generator are rigorously controlled within guideline operating ranges.

Limited extrapolations suggest that the Model F heat exchangers with Alloy 600 TT tubes now at Seabrook 2 should provide 20 to 25 years service at the Trojan Plant, particularly if some deficiencies indicated in Section 6.1 are corrected. Similar heat exchangers now in service have provided over 10 years service with no tubes plugged because of cracking. New heat exchangers with Alloy 690 TT could provide at least an additional 30 to 35 years service at the Trojan Plant if secondary-side performance is amply represented by available laboratory tests. Based on compatibility with the primary coolant, the margin of improvement provided by the Alloy 690 TT should be even greater. However, because of the complexity of the secondary system environment in localized regions, the margin of improvement over Alloy 600 TT could be lower.

OPTIONS FOR TROJAN SG REPLACEMENT

Selection of either a) the Seabrook SGs (with precautions indicated in point 11 of the conclusions) or b) a SG with Alloy 690 TT tubes seems substantially justified on materials grounds. Economic and political considerations can then enter strongly into the decision process.

NOMENCLATURE

°C	degree centigrade
Alloy 600	Inconel 600
Alloy 690	Inconel 690
Alloy 800	Incoloy 800
AVT	all volatile treatment
BPA	Bonneville Power Administration
C	carbon
Cr	chromium
Elong	elongation
Fe	iron
Fret (LP)	fretting by loose parts
Fret (Preh)	fretting in preheater
Fret (AVB)	fretting by antivibration bar
g/L	grams per liter
h	hours
ID	inside diameter
IGA	intergranular attack
Inconel®	Nickel-base alloy (see Appendix A, Table A1)
$K_{I_{SCC}}$	threshold stress intensity factor for stress corrosion cracking
KWU	Kraftwerk Union
m	meters
MA	mill annealed
min	minimum
MPa	megapascal
Ni	nickel
OD	outside diameter
PNL	Pacific Northwest Laboratory
PWR	pressurized water reactor
PWSCC	primary water stress corrosion cracking
RUB	reverse U bend
SCC	stress corrosion cracking
sen	sensitized
SG	steam generator

SG-years	steam generator years
SP	support plate
Spec	specification
TS	tube sheet
TT	thermally treated
UB	U bend
UTS	ultimate tensile strength
WOL	wedge opening load
YS	yield strength

CONTENTS

1.0	INTRODUCTION	1.1
2.0	APPROACH	2.1
3.0	CONCLUSIONS AND RECOMMENDATIONS	3.1
4.0	EVALUATION OF REACTOR SERVICE EXPERIENCE INVOLVING ALLOY 600 TT AND ALLOY 690 TT SG TUBES	4.1
4.1	EXPERIENCE IN U.S. REACTORS	4.1
4.2	SPECIFIC COMPARISONS OF SG PERFORMANCE IN COMPANION REACTORS	4.4
4.2.1	Catawba Units 1 and 2	4.4
4.2.2	Byron Units 1 and 2	4.4
4.2.3	Other Comparisons	4.4
4.2.4	Summary of Comparisons in Companion Reactors	4.5
5.0	EVALUATION OF LABORATORY TEST RESULTS FOR INCONEL 600 AND INCONEL 690	5.1
5.1	COMPARISON OF CRACKING PROPERTIES	5.1
5.2	SECONDARY SIDE CONSIDERATIONS	5.3
5.3	INFLUENCE OF MICROSTRUCTURE	5.6
5.4	INFLUENCE OF OPERATING PARAMETERS	5.7
6.0	BASIS FOR ESTIMATING THE SERVICE LIFE OF THE SEABROOK UNIT 2 SGs	6.1
6.1	GENERAL OBSERVATIONS	6.1
6.2	TECHNICAL BASIS	6.2
6.3	INDUSTRY COMMENTS REGARDING SG LONGEVITY	6.3
7.0	REFERENCES	8.1
	APPENDIX A - TABLES A1 THROUGH A4	A.1

TABLES

1.	Service Experience - Inconel 600 TT and Inconel 690 TT	4.2
2.	Characterization of Reactor Experience Base for Alloy 600 TT and Alloy 690 TT SG Tubes in U.S. Reactors	4.3
3.	Comparison of Catawba Units - Characteristics and Status	4.5
4.	Period Before Cracking in PWR SG Tube Alloys in Simulated Primary Coolant	5.3
5.	$K_{I_{SCC}}$ for Alloys 600 MA, 600 TT, 690 MA, and 690 TT in 100 g/l NaOH	5.4
6.	Laboratory Experience - Inconel 600 MA and TT and Inconel 690 MA and TT in Reactor Primary Coolant	5.4
7.	Laboratory Experience - Inconel 690 and Inconel 600 TT in Secondary Fluid	5.5

1.0 INTRODUCTION

After 15 years of operation, the Trojan Series 51 steam generators (SGs) have degraded due to several corrosion mechanisms to the degree that replacement is being considered. The SG tubes are Alloy 600 mill annealed (MA). Appendix A compares properties (Table A1) and corrosion characteristics (Table A2) of candidate tube materials. SG design and operating conditions are briefly outlined in Table A3 for Trojan and Table A4 for Seabrook SGs.

The Bonneville Power Administration (BPA) requested that the Pacific Northwest Laboratory (PNL)^(a) evaluate, from a materials standpoint, two options for replacement of the degraded SGs at the Trojan nuclear power plant:

- acquisition of four Model F SGs manufactured in 1981 for the cancelled Seabrook Unit 2 reactor, for near-term installation at Trojan
- acquisition of replacement SGs manufactured with advanced materials and designs, but having a procurement time of 3 to 4 years.

The specific materials issues requested for this assessment are:

- the relative merits of Inconel 600 thermally treated (TT), characteristic of tubes in the Seabrook SGs, versus Inconel 690 TT that is being installed in new SGs
- the basis to project how long the Seabrook SGs can be expected to operate without replacement.

(a) Pacific Northwest Laboratory is operated by Battelle Memorial Institute for the Department of Energy under Contract DE-AC06-76RLO 1830.

2.0 APPROACH

The assessment of SG options focused on:

- reactor service experience for Westinghouse SGs in U.S. plants that have Alloy 600 TT tubes, including plants with replacement SGs and recent plants that began operation with Model F SGs, of the type available in the Seabrook Unit 2 SGs
- reactor service experience for replacement SGs having Alloy 690 TT tubes
- laboratory data for Alloy 600 and Alloy 690, emphasizing studies that compared the properties of the two alloys side-by-side
- an overview of Trojan SG characteristics and operation for relevance to expected operation of replacement SGs (Appendix A, Table A3)
- an overview of Seabrook Unit 2 SG characteristics (Appendix A, Table A4).

3.0 CONCLUSIONS AND RECOMMENDATIONS

The relative integrity of Alloy 600 TT and Alloy 690 TT for SG tube application was reviewed, involving two data bases: actual service in SGs and laboratory studies. Conclusions and recommendations from the review are summarized below.

1. Selection of either option: a) Seabrook SGs (with the precautions indicated in point 11 of this section) or b) SGs with advanced designs and Alloy 690 TT tubes seems substantially justified on materials grounds for 20 to 25 years of additional operation at the Trojan reactor. Economic and political considerations, therefore, can enter strongly into the decision process.
2. Alloy 600 TT is in service in about 80 Model F SGs worldwide (about 50 in the U.S.), representing 430 SG-years^(a) (290 SG-years in the U.S.). The longest service time is 11 to 12 years. Tube plugging has been minimal (0.09% of total tubes plugged due to manufacturing defects, fretting, etc.). No case has been reported of Alloy 600 TT tubes being plugged due to corrosion phenomena in U.S. plants (data for some foreign plants were not found in the review process).
3. Alloy 690 TT is in service in three reactors (two U.S., one Swedish), representing 30 SG-years. The maximum service time is about 3 years. No tube pluggings have been reported for any cause. In the three plants, steam pressures have been lower than expected, possibly due to lower thermal conductivity for Alloy 690, although other factors may contribute.
4. Numerous laboratory investigations have been published that involved corrosion studies on Alloy 600 and Alloy 690 in multiple metallurgical conditions (Appendix A, Table A2). Laboratory data are available for periods up to four years in primary coolant chemistry and up to eight years in secondary system chemistry. In the studies, Alloy 690 has consistently exhibited superior immunity to stress corrosion cracking (SCC) under pressurized-water reactor (PWR) primary coolant conditions and in normal all volatile treatment (AVT) conditions. Alloy 690 also has superior corrosion and cracking resistance in secondary side upset chemistry conditions. Extrapolation of accelerated test results suggests that SGs with Alloy 600 TT could provide up to 20 to 25 years of service and Alloy 690 (MA or TT) could provide up to 30 to 35 years of service.
5. Alloy 690 has emerged as the solid leader in corrosion and cracking resistance in laboratory tests. Alloy 600 TT has the more substantial

(a) SG-year = steam generator year, i.e., one SG in service (at power or shut down) for one year.

reactor service history. Both Alloy 690 TT and Alloy 600 TT have superior laboratory corrosion resistance to Alloy 600 MA that has had a poor history of performance in SG applications, including service in the Trojan SGs.

6. The emerging impressive reactor performance of SGs with Alloy 600 TT tubes (i.e., no corrosion-induced tube plugging in up to 11 years of service time) must be interpreted not just in terms of improved material properties, but also reflecting improved crevice design, support plate and tube sheet materials, and water chemistry control, among other factors.
7. The reactor performance of Alloy 690 TT has also been successful, but it would be premature to base long-term decisions on current, limited, short term results under reactor service conditions. However, combined with superior performance in extensive laboratory tests, Alloy 690 TT has numerous proponents as the material of choice for extending the successful operation of SGs. Other investigators recommend caution until the reactor data base is more extensive.
8. While the Alloy 600 TT and 690 TT tube materials have performed well in laboratory tests under upset chemistry conditions, behavior of the advanced SG materials and designs under upset conditions has not yet been substantially challenged in reactor service.
9. The emerging successful performance of Model F SGs and improved laboratory corrosion performance of Alloy 600 TT (compared to Alloy 600 MA) suggest that the Seabrook Unit 2 Model F SGs have validity as replacement candidates for the degraded Trojan SGs. With now over a decade of Model F SG service without tube plugging due to corrosion, satisfactory service times of 20 to 25 years seem possible, though not assured (depending on the response to serious upsets and possible impacts of other Seabrook SG vulnerabilities).
10. From a materials standpoint, the following considerations must be weighed:
 - Is there sufficient evidence for confidence that the Seabrook SGs will provide satisfactory service at Trojan through the current 40-year license period (25 more years)? The positive service performance of Model F SGs for over a decade and superior behavior of Alloy 600 TT materials in laboratory tests, compared to Alloy 600 MA, offer favorable evidence that satisfactory operation of Model F SGs is a reasonable expectation for periods of 20 to 25 years, given nominal operating conditions (e.g., temperatures) and satisfactory water chemistry control. It seems premature to also project satisfactory performance of Model F SGs through the license renewal period (up to 20 years beyond the current 40-year license), if that is a consideration for the Trojan reactor.
 - Is there sufficient evidence for confidence that SGs with Alloy 690 tubes will provide satisfactory service through the remaining

25 years of the current 40-year license period? Also, through up to 20 years of additional service in extended operation? The principal basis for judgement of Alloy 690 TT behavior is extensive laboratory testing. Because Alloy 690 specimens did not fail in laboratory tests, a bound is not established. Our extrapolation of the laboratory data from 360°C to 330°C (near the Trojan hot leg temperature of 325°C) suggested that the specimens would remain unfailed after 30 years. The limited service experience with Alloy 690 TT tubes in SGs does not contribute substantially to the basis for extrapolation. However, the favorable experience with the improved design and operation of Model F SGs seems relevant. If the Model F SGs had been tubed with Alloy 690 TT tubes, the laboratory data suggest that the performance would have been without corrosion-induced failures as has been the case with Alloy 600 TT tubes. Therefore, the basis for optimism for Model F SG to operate through the remainder of the current Trojan license seems equally justified for units tubed with Alloy 690 TT. There is insufficient evidence that Alloy 690 can be relied on for current operation plus the full term of license renewal.

11. A decision regarding the Seabrook SG units should factor in other considerations, including the following:
 - Have lay-up conditions during over a decade of storage been adequate to preclude degradation?
 - What over-checks on materials are warranted to assure that specifications are uniformly met throughout the SGs?
 - Has the Seabrook SG design been analyzed sufficiently for deficiencies (e.g., character of quatrefoil broaches, Alloy 600 components such as drains and channel divider plate, and anti-vibration bar and flow baffle design)?
 - Have the prospects for, and consequences of, prospective upgrades (e.g., replacement of carbon steel J tubes and flow ring) been adequately considered?
 - Are the projected operating conditions for the replacement SGs at Trojan within the envelope of conditions (e.g., temperature and water chemistry) that have been conducive to highly favorable service performance of Model F SGs?

4.0 EVALUATION OF REACTOR SERVICE EXPERIENCE INVOLVING ALLOY 600 TT AND ALLOY 690 TT SG TUBES

Corrosion-induced failures of tubes in original PWR SGs has been a costly and troublesome problem. That experience contrasts with vastly improved performance of new and replacement SGs that have improved designs and materials. The favorable service experience is summarized in this section.

4.1 EXPERIENCE IN U.S. REACTORS

Reactor service for three groupings of SGs is summarized in Table 1.

- A. Replacement SGs with Alloy 600 TT tubes installed in U.S. reactors
- B. Original SGs of Type F and D5 with Alloy 600 TT tubes installed in U.S. reactors
- C. Replacement SGs with Alloy 690 TT tubes at two U.S. reactors and one Swedish reactor

Key features of the reactor experience base are provided in Table 1 for Alloy 600 TT and Alloy 690 TT, and are summarized in Table 2. The longest service is about 11 years for Alloy 600 TT tubes (in 1992) and about 3 years for Alloy 690 TT.

From Table 2, the cumulative service time for SGs with Alloy 600 TT tubes operating in U.S. plants is 290 SG-years. The corresponding number for SGs with Alloy 690 tubes is about 30 SG-years.^(a)

Tube plugging data (Dow 1991) indicate that no tubes were plugged due to any corrosion mechanism for the SGs addressed in Table 1. The significance of that observation is that corrosion-induced tube plugging was prevalent in early operation of numerous SGs. For example, tube plugging due to corrosion began after 2 years in Surry Unit 1 and after 1 year in Surry Unit 2 for the

(a) There are 84 Model F SGs worldwide with operational experience, representing 432 SG-years of service. In 1991 only 0.09% of the tubes had been plugged, involving less than 1 tube plugged per SG per year of operation. Most, but not all tubes in Model F SGs are Alloy 600 TT. For example, in Callaway, both TT (first 10 rows) and MA conditions are represented.

TABLE 1. Service Experience - Inconel 600 TT and Inconel 690 TT

	Reactor	SG Type	Tube Material	Date of Operation ^(a)	Tubes Plugged Through 1990 ^(b)	Operating Experience Through 1990
A	INCONEL 600:					
	Surry-1	51F	600 TT	07/81 R	10	No tubes plugged due to corrosion.
	Surry-2	51F	600 TT	09/80 R	3	Same as above.
	Turkey Point-3	44F	600 TT	04/82 R	59	Same as above.
	Turkey Point-4	44F	600 TT	05/83 R	34	Same as above.
	Point Beach-1	44F	600 TT	03/84 R	3	Same as above.
	Robinson-2	44F	600 TT	10/84 R	2	Same as above.
B						
	Braidwood-2	D5	600 TT	10/88 O	0	Same as above.
	Byron-2	D5	600 TT	08/87 O	43	Same as above.
	Callaway	F	600 MA ^(c) 600 TT	12/84 O	73	No pitting or denting of concern after 5 years. No tubes plugged due to corrosion.
	Catawba-2	D5	600 TT	08/86 O	48	Same as above.
	Millstone-3	F	600 TT	04/86 O	16	No tubes plugged due to corrosion.
	Vogtle-1	F	600 TT	05/87 O	11	Same as above.
C						
	INCONEL 690:					
	Ringhals-2	KWU/GHH	690 TT	??/89 R	0	Minimal service time.
	D.C. Cook-2	51F	690 TT	03/89 R	0	Same as above.
	Indian Point-3	44F	690 TT	05/89 R	0	Same as above.
	Wolf Creek	F	600 TT	09/85 O	39	Same as above.

Based on data in 1) Steam Generator Progress Report Revision 7, September 1991; and 2) "Status of Steam Generators at U.S. PWRs," Nucl. Wk., August 3, 1989, pp. 13-15.

- (a) R denotes replacement SGs; O denotes original SGs.
- (b) At some plants a major fraction of the plugged tubes were plugged before SG operation.
- (c) First 10 rows TT; remaining tubes MA.

TABLE 2. Characterization of Reactor Experience Base for Alloy 600 TT and Alloy 690 TT SG Tubes in U.S. Reactors

I. Longest Service Time (Through Early 1992)

Alloy 600 TT: original SG is 7 years; replacement SG is 11 years

Alloy 690 TT: replacement SG is 3 years

II. Total Service Time (Through Early 1992)

	<u>No. of Reactors^(a)</u>	<u>No. of SGs</u>	<u>Total Service Time, SG-Years</u>
Alloy 600 TT	13	49	290
Alloy 690 TT	3 ^(b)	11	30

III. Tubes Plugged Due to Corrosion (Through 1990)

Alloy 600 TT: zero

Alloy 690 TT: zero

(a) Westinghouse reactors at U.S. plants for Alloy 600 TT.

(b) Two U.S. and one Swedish reactors.

original SGs. Similar comparisons are valid for other reactors having replacement SGs. However, for the replacement SGs, no tubes have been plugged due to corrosion through 1990 (after 9 and 10 years, respectively).

The absence of corrosion-induced plugging results from numerous factors, including (but not limited to) improved water chemistry, removal of secondary-side copper sources, improved sludge management, improved SG design, and materials, including 400-series tube sheets and support plates, and more corrosion-resistant tube materials.

The three reactors operating with Alloy 690 SG tubes have reported steam pressures that are less than expected, resulting in a concomitant decrease in power production. The phenomenon is hypothesized to be due to lower thermal conductivity for Alloy 690, compared to Alloy 600 (see Table A1). However, other factors may contribute to the lower steam pressures (*Nucleonics Week* et al. 1990).

4.2 SPECIFIC COMPARISONS OF SG PERFORMANCE IN COMPANION REACTORS

Comparisons of SG performance in companion reactors can be instructive, but conclusions must be drawn with caution due to potential differences in SG design and operating conditions. In most cases, the comparisons are drawn between SGs with Alloy 600 MA tubes in one plant and Alloy 600 TT tubes in the companion plant.

4.2.1 Catawba Units 1 and 2

The characteristics and status of the two Catawba units are compared in Table 3. Catawba Unit 1 has had both inner diameter (ID) and outer diameter (OD) corrosion indications while Catawba Unit 2 has not plugged tubes due to corrosion. Catawba Unit 1 has operated one year longer, but began to show corrosion indications after only 2 to 3 years. Catawba Unit 2 has not plugged tubes due to corrosion after 3 to 4 years.

A comparison of properties for tubes in the Catawba SGs revealed substantial differences that reportedly resulted from a thermal treatment that was shorter than specified for one batch of tubes.

The absence of corrosion indications for Catawba Unit 2 is consistent with improved design and higher integrity materials (Table 3).

4.2.2 Byron Units 1 and 2

Byron Unit 1 (09/85 operation) has Alloy 600 MA SG tubes, a carbon steel support plate, and drilled support plate holes; while Byron Unit 2 (08/87 operation) has Alloy 600 TT SG tubes, a stainless steel support plate, and a quatrefoil support plate crevice. Through 1990, Byron Unit 1 has plugged 43 tubes due to ID corrosion indications while Byron Unit 2 has not plugged tubes due to corrosion, but began operation two years later.

4.2.3 Other Comparisons

Braidwood Units 1 and 2 began operation in 1988. The SG tubes are Alloy 600 MA at Unit 1 and Alloy 600 TT at Unit 2. Neither unit has plugged tubes for corrosion reasons, but the operating time is relatively short.

Cook Unit 1 (08/75 operation) still operates with the original Model 51 SGs (713 tubes plugged due to corrosion). The Cook Unit 2 Model 51 SGs were

replaced in 1988 (561 tubes plugged due to corrosion and 378 due to other causes) with Model 51 SGs with Alloy 690 TT tubes. The higher susceptibility of the Cook Unit 1 tubes to ID SCC was regarded by a company spokesman as due to a difference in SG fabrication (*Nuc1. Wk.*, August 3, 1988).

4.2.4 Summary of Comparisons in Companion Reactors

In general, the operating times for SGs addressed in the above comparisons of plant pairs are not long enough to draw major conclusions. However, to date, tube plugging due to corrosion has been necessary for most units having older designs and materials and has been essentially zero for newer designs and materials.

TABLE 3. Comparison of Catawba Units - Characteristics and Status

Characteristic	Catawba Unit 1 Status	Catawba Unit 2 Status
Initial operation	6/85	8/86
SG model	D3	D5
Tube material	600 MA	600 TT
Tube support material	Carbon steel	Stainless steel
Support plate hole	Drilled hole	Quatrefoil
Tube/tube sheet	Full/roll	Full/hydro
Tube plugging: ^(a)		
• OD S/IGA SP	17	0
• ID SCC TS	193	0
• ID SCC UB	1	0
• Fret (Preh)	3	0
• Fret (AVB)	0	14
• Fret (LP)	0	10
• Other (non-corrosion)	42	24

(a) Through 1990.

5.0 EVALUATION OF LABORATORY TEST RESULTS FOR INCONEL 600 AND INCONEL 690

Laboratory testing has been conducted primarily under conditions of constant stress, constant strain rate, stressed C-ring tests, reverse U-bend tests, and pressurized tubes. The objectives of these tests have been to characterize the degradation phenomena of 1) primary water stress corrosion cracking (PWSCC) at roll transitions, U-bends, and dents of recirculating steam generators, 2) secondary side intergranular attack/stress corrosion cracking (IGA/SCC) at tube supports, in tube sheet crevices, and in sludge piles of recirculating steam generators, and 3) erosion-corrosion in once-through steam generators. These tests have been conducted in controlled water at temperatures ranging from 360°C to 400°C in steam; these temperatures are higher than typical hot leg temperatures in steam generators and, therefore, are considered to be accelerated tests. The importance of accelerated tests is that testing and steam generator experience with Inconel 690 is limited to eight and less than five years, respectively. Accelerated tests provide early comparative information, but do not directly predict service lifetimes.

5.1 COMPARISON OF CRACKING PROPERTIES

As indicated in Section 3, cracking of Inconel 690 TT or 600 TT has not been observed through the latest reported inspections (1990) under steam generator service conditions. Inconel 690 TT and MA appears to be superior to Inconel 600 TT and MA in most mechanical and corrosion laboratory tests. The thresholds for cracking in Inconel 690 MA and TT have only been detectable in accelerated tests or under abnormally severe test conditions. Under primary water conditions, the threshold for cracking in Inconel 690 TT appears to be unbounded. Cracking from the secondary side may be the limiting factor. However, the data base is insufficient to quantitatively characterize the performance margin of Inconel 690 TT over Inconel 600 TT in terms of SG years. A summary of French and other work on SCC of SG tubing materials has been provided by Gras (1991). McIlree, Olberg and Nestell (1985) have published a steam generator reference book.

Reverse U-bend (RUB) specimens tested for periods up to 33,000 hours to show time to cracking (Norrington, Stiller, and Nilsson 1991) indicate that the

cracking resistance of Inconel 690 MA and 690 TT is superior to that for Inconel 600 TT which is superior to Inconel 600 MA. The results are summarized in Table 4. Tests with Alloys 600 TT and 690 TT extended only to 23,000 hours. Because the test temperatures are higher than the Trojan hot leg temperature, these represent accelerated tests. When these results were extrapolated to 330°C (near the Trojan hot leg temperature of 325°C) using the temperature dependence for initiation of crack propagation given by Gras (1991), then the predicted period to the onset of cracking was extended longer, also shown in Table 4.

The extrapolation is based on the relationship given by Gras:

$$t_c = A \exp(22000/T) \quad [1]$$

where t_c is the time-to-cracking evolution and T is temperature in Kelvin. The extrapolation is based primarily on data for Inconel 600 MA. The value of A depends on microstructure, microchemistry, stress and strain history, heat exchanger design features, hot leg temperature, and water chemistries of the primary and secondary systems. The reliability of an extrapolation from the test temperature to the Trojan hot leg temperature is also subject to unknown factors, e.g., variability in the performance of sibling steam generators operated similarly at companion nuclear plants. However, Equation 1 provides a basis for evaluating the potential for performance improvement offered by the Inconel 690 TT over the Inconel 600 TT.

TABLE 4. Period Before Cracking in PWR SG Tube Alloys in Simulated Primary Coolant

Alloy	Period Before Cracking, hours	
	365°C Data	330°C Predicted
Inconel 600 MA	1,000 to 11,000	7,000 to 80,000
Inconel 600 TT	23,000 ^(a)	170,000
Inconel 690 TT	>23,000 ^(b)	>170,000
Inconel 690 MA	>33,000 ^(b)	>240,000

- (a) Cracks were found in two of four specimens.
 (b) No cracks were found.

The comparison of Inconel 690 MA and TT to Inconel 600 MA and TT in Table 4 predicts cracking in Inconel 600 MA between one and ten years. This is similar to service history. The period of extrapolated data representing about 20 years (170,000 hours) for Alloy 600 TT (two of four specimens cracked at the 360°C test temperature) is not verified by experience, because the oldest steam generator with Alloy 600 TT tubes has only operated for approximately 10 years. However, the 20-year extrapolation is not inconsistent, because no Alloy 600 TT tubes have been plugged due to cracking in up to 10 years of reactor service.

The comparison may be conservative, because the tests were not conducted long enough to produce cracking in the Inconel 690 specimens. Comprehensive data bases on the temperature dependence for crack initiation for the thermally treated Inconel 600 and 690 alloys do not appear to be available. The results for Inconel 690 MA are included in Table 4 because they imply that even if Inconel 690 components were not uniformly heat treated, the resistance to cracking would likely exceed that for the Inconel 600 alloy.

5.2 SECONDARY SIDE CONSIDERATIONS

The values of threshold stress intensity, $K_{I_{SCC}}$, obtained from Alloy 690 wedge opening load (WOL) specimens in caustic were significantly higher than for Inconel 600 based on a summary by Gold et al. (1990). The results are shown in Table 5. In a solution with a lower caustic concentration, 4 g/L NaOH, the threshold stress intensity nearly doubled for Inconel 600 MA and TT, but cracking was not propagated in Inconel 690 MA or TT. The threshold stress intensity defines the load condition required to propagate cracking.

The test data in reactor primary coolant with the longest duration extend to approximately 4 years (Table 6). The test data in secondary steam generator water with the longest duration extend to approximately 8 years (Table 7). Because of limited testing time, some tests were conducted under extreme temperature, stress, strain rate, or chemically concentrated conditions. These conditions represent accelerated tests. The number of the longest term tests had limited scope and, therefore, do not provide a broad

TABLE 5. $K_{I_{SCC}}$ for Alloys 600 MA, 600 TT, 690 MA, and 690 TT in 100 g/L NaOH (Gold et al. 1990)

Inconel Alloy and Condition	$K_{I_{SCC}}$, psi-in ^{0.5} in 100 g/L NaOH
600 MA	8,300
600 TT	11,600
690 MA	14,800
690 TT	21,100

TABLE 6. Laboratory Experience - Inconel 600 MA and TT and Inconel 690 MA and TT in Reactor Primary Coolant

Inconel Alloy	Test Period, h	Test Type	Summary of Results	Solution	Reference
600 MA 600 TT 690 MA 690 TT	<11,000 23,000 >33,000 >23,000	RUB ^(a)	600 TT: 2 of 4 specimens cracked within 23000 h 690 MA not cracked in 33,000 h; 690 TT not cracked in 23,000 h	365°C water with hydrogen	Norrington, Stiller, and Nilsson, 1991
690 MA 690 TT	16,000 16,000	RUB	Observed no cracking	360°C primary water	Smith et al. 1985
690 MA 690 TT	12,000 12,000	RUB	Observed no cracking	360°C primary water	Gimond et al. 1985
690 MA 690 TT	10,000 10,000	RUB	Observed no cracking	360°C primary water	Yonezawa et al. 1985
690 TT	4000	RUB	No cracking	400°C, 3000 psi steam with hydrogen	Aspden et al. 198
690 MA	7200	RUB	No cracking	400°C steam	Gold et al. 1990
690 MA 690 TT	31,000	RUB	No cracking	360°C water with hydrogen	Santarini et al. 1989
690 MA 690 TT	6,000	RUB	No cracking	400°C steam	Santarini et al. 1989
600 MA 690 TT	1500	Dissolution by corrosion	600 MA corrosion 4 to 6 times higher than for 690 TT	330°C primary coolant	Gold et al. 1990

(a) Reverse U bend test.

TABLE 7. Laboratory Experience - Inconel 690 and Inconel 600 TT in Secondary Fluid

Inconel Alloy	Test Period, h	Test Type	Summary of Results	Solution	Reference
600 MA 600 TT 690 MA 690 TT	- - - -	WOL ^(a) specimens tested in caustic solutions	Threshold stress intensity highest for 690 MA and TT	350°C, 200 g/L NaOH	Smith et al. 1985
690 TT	76,000	C-Ring	No cracking	Numerous caustic solutions	Smith et al. 1985
690 TT		Pressurized capsules	No cracking	Numerous caustic solutions	Smith et al. 1985
690 TT	12,000	RUB ^(b)	No cracking	350°C 10% NaOH	Santari-ni et al. 1989
690 TT	12,000	C-Ring	No cracking	350°C 10% NaOH	Santari-ni et al. 1989
690 TT	4,000	C-Rings	No cracking	288 to 300°C acid chloride	Yonezawa et al. 1985
690 TT	4,000	RUB	No cracking	288 to 300°C acid chloride	Yonezawa et al. 1985
690 TT	1500	C-Rings 150% YS ^(c)	No cracking	343°C 10% NaOH	Yonezawa et al. 1985
690 TT 690 MA	36,790	RUB	No cracking	288 to 360°C in AVT ^(d) water	EPRI NP-576-1SP
690 TT 690 MA	71,000	C-Rings	No cracking	288 to 343°C in AVT water	EPRI NP-5761S

(a) Wedge opening load.

(b) Reverse U bend test.

(c) Yield strength.

(d) All volatile treatment.

statistical data base. However, the differences between Inconel 600 and 690 appear to be significant, even with the limited data base. The WOL value was higher for Alloy 690 TT than for Alloy 600 TT at 350°C in 200 g/L caustic (Smith et al. 1985). Procedures to extrapolate for longevity predictions under service conditions are complex and may be misleading because of the many variables in material condition and operating parameters that may not be adequately accounted for. These comments also apply to the predictions made in Table 4. Therefore, control of plant operation may be nearly as important as the selection of an alloy.

Accelerated dissolution corrosion tests have failed to reveal a superiority of Alloy 690 over Inconel 600. Wastage in Inconel 690 exceeded wastage in Alloy 600 during accelerated testing of stressed C rings in solutions containing acid sulfates, with or without chlorides (Cullen et al. 1991). Likewise Alloy 690 suffers wastage similar to Alloy 600 in organic acid solutions. Therefore, the relative benefits of Alloy 690 over Alloy 600 characteristic of tests in primary coolant conditions are less favorable for some conditions that simulate upset secondary water chemistries.

5.3 INFLUENCE OF COMPOSITION AND MICROSTRUCTURE

Improved resistance to cracking in alloys containing more than 18% chromium (Cr) has been the reason for manufacturing and research on a modified Alloy 600 with 19% Cr. This alloy behaves better than normal Alloy 600 (Donati et al. 1987). The higher Cr content is likely an important factor for the superior performance of Alloy 690. The higher Cr content may play a role in providing a passive surface that is more resistant to hydrogen and impurity species. Factors that affect the corrosion and cracking resistance include (but are not restricted to):

- carbon and Cr concentrations and distribution (heat treatment)
- residual stresses from fabrication and incomplete weld sections (stress relief)
- high temperature mill anneal (best for Inconel 600, but still susceptible)
- low temperature mill anneal

- low angle grain boundaries better than intermediate and high angles (Crawford and Was 1991)

Laboratory testing has indicated that the yield stress for thermally treated Inconel 690 should not exceed 56,000 psi (Amar and Shah 1991). This upper limit on yield stress tends to reduce the potential for cracking by limiting deleterious cold working and residual stresses.

5.4 INFLUENCE OF OPERATING PARAMETERS

In addition to water chemistry parameters already addressed, other operating parameters have been recognized to have important effects on heat exchanger degradation. Variables in operating parameters that may impact service longevity are:

- Low lead (Sakai et al. 1991); the corrosion of annealed Alloy 600 and thermally treated Alloy 690 was increased by lead, but the corrosion of Alloy 690 tended to be more transgranular, rather than intergranular. (Miglin et al. 1991); Accelerated tests with Inconel 600 MA C-ring specimens in water enriched with lead at 360°C indicated that lead induces and propagates cracking.
- Zinc addition (Esposito et al. 1991); addition of 20 ppb zinc decreased the corrosion rate for 600 TT and 690 TT and increased the crack initiation times for 600 MA and 600 TT by factors of up to four during highly stressed reverse U-bend testing.
- Hot leg temperature; the kinetics of degradation phenomena are increased with increasing hot leg temperature.

6.0 BASIS FOR ESTIMATING THE SERVICE LIFE OF THE SEABROOK UNIT 2 SGs

The basis to estimate the service life of the Seabrook Unit 2 Model F SGs depends on the past decade of highly favorable Model F SG service, results of extensive laboratory testing, and our extrapolation of the laboratory results to the Trojan hot leg temperature (325°C). Several caveats are identified that might influence the SG performance.

6.1 GENERAL OBSERVATIONS

Estimates of SG service life were frustrating in the decades of the 1960s and 1970s. Tube plugging due to corrosion began in the early years of operation and multiplied in many units to a magnitude requiring costly replacements.

Now there is emerging evidence that the factors that determine SG integrity may be largely understood and under control. That evidence is represented in part by the service experience summarized in Table 2. Units have operated for up to a decade without tube plugging due to corrosion.

However, while there is a growing basis for optimism, this is also a time for cautions and caveats.

- While AVT chemistry has mitigated denting, the lack of buffering action leaves crevices potentially vulnerable to pH excursions into corrosive regimes. The optimum approach to water chemistry control, use of inhibitors, etc., may not yet have fully emerged. However, incorporation of improved crevice designs mitigates crevice corrosion.
- The resistance of the advanced designs and materials to severe episodes of impurity ingress seems yet to be tested, even though laboratory studies indicate that advanced tube materials are more resistant to faulted secondary-side conditions than the Alloy 600 MA material (Appendix A, Table A2).
- Indications that some SG materials have not fallen uniformly within specifications suggests that units such as Seabrook Unit 2 need to undergo sufficient scrutiny and perhaps over-checks to ensure that potential vulnerabilities are recognized. Other areas to be considered are anti-vibration bar and flow baffle design, flow ring and J-tube materials, and the long-term behavior of Inconel components other than the tubes (e.g., drains and channel divider plate).

- Some reactor staff, with management support, have given high priority to rapidly correcting upset chemistry conditions, sometimes at the expense of power production. The lifetime of a given set of SGs will be influenced by management philosophy and staff diligence.

6.2 TECHNICAL BASIS

The data bases reviewed in Sections 4 and 5 have the following relevance to the Seabrook Unit 2 SG units:

- The Seabrook units are Model F SGs that relate to the substantial and, so far, successful experience summarized in Section 4.
- The Seabrook units are tubed with Alloy 600 TT that has markedly improved corrosion resistance, compared to early Alloy 600 metallurgical conditions, based on comparative laboratory corrosion tests summarized in Section 5.

Extrapolation of laboratory data was conducted from a study of primary-side SCC and conducted at 360°C on four specimen categories: Alloy 600 MA and TT; and Alloy 690 MA and TT. The data were extrapolated to 330°C, near the maximum Trojan hot leg temperature of 325°C. Cracking for 600 MA condition was estimated to occur in the period of 1 to 10 years, consistent with SG reactor service experience. The 600 TT condition estimate suggested that cracking could be expected to begin at about 20 years. The data for 690 TT was extrapolated to 20 years without cracking, and for 690 MA the extrapolation was 30 years without cracking (due to longer autoclave run times for the 690 MA specimens). The assumption, based on SG operating experience, is that even if the onset of cracking were to occur at about 20 years, the Seabrook SGs might be expected to operate for at least another five years before replacement would be required. With the advanced SG design and more corrosion-resistant tube material, the useful life might be extended even further. However, some vulnerabilities in the Seabrook Unit 2 SGs may need to be dealt with. For example, eddy current indications have been observed at drilled support plate locations in a Palo Verde SG. The extent of the problem is unknown. Sleeving seems to offer a method to mitigate tube degradation at the baffle plate, if necessary.

Based on data found in the review, parallel extrapolations for secondary-side corrosion phenomena did not seem justified, under the scope of

this investigation. Therefore, judgements regarding longer-term secondary-side behavior of the SG materials are based on extensive accelerated autoclave data showing no cracking for either the Alloy 600 TT or Alloy 690 TT materials. However, Appendix A, Table A2 suggests that extending the life of the Seabrook Unit 2 SGs would depend on the satisfactory control of chlorides and sulfates.

The combination of substantial, successful Model F SG reactor service and evidence of improved corrosion resistance of thermally-treated Alloy 600, provides a positive basis for optimism that the Seabrook units can be expected to operate with adequate integrity for 20 to 25 years, with caveats indicated in Section 6.1.

6.3 INDUSTRY COMMENTS REGARDING SG LONGEVITY

It seems significant to note that plant spokesmen have sufficient confidence in the understanding of prior SG problems and the emerging positive service experience to go on record to the effect that they expect their SGs to serve the plant through its end of life. Examples of statements affirming this confidence in the performance of Model F SGs with Inconel 600 TT tubes appear in the following references:

- Surry-1 and -2, *Nucleonics Week*, July 27, 1989
- D. C. Cook, *Nucleonics Week*, July 27, 1989
- Callaway, *Nucleonics Week*, August 3, 1989

For example, the Callaway SG units began operation in 1984, so the utility spokesman is presumably projecting satisfactory operation over the 40-year period of the current license.

Confidence in SGs tubed with Alloy 690 TT also is evident from the fact that three reactors are on line with tubes of that material and others are on order. However, proponents of Alloy 800 can also be found, and some investigators feel that "the jury is still out" on Alloy 690.

In a special report, problems with the Inconels and the status of their solutions (*Nucleonics Week* et al. 1990) were addressed. Corrosion expert Phillipe Berge, of Électricité de France (EdF), was quoted as saying

"Personally, I am very confident in this material. Not that it will never leak. You can have loose parts, for example. But since 1981, we have thought it's the best optimization, and tests in those nine years have only confirmed that hypothesis." Berge is further quoted: "We can say that the problem of cracking [of Alloy 690] in primary water can be ruled out....We have worked with this material more than any other material...There's a fantastic sum of data."

In France, Inconel 690 has been subjected to a test rig, simulating years of operation in an environment similar to a PWR primary circuit. Framatome spokesman Georges Slama said "I know of no material which has been so thoroughly tested. All of its characteristics are equal or superior to anything else on the market. Even in a sulfurous environment, where Inconel 690 will crack, you need more sulfur than for the other alloys, especially Inconel 600, which is very sensitive."

Again quoting from *Nucleonics Week* et al. (1990): "U.S. experts say they expect most if not all utilities to select Inconel 690 over Inconel 600 when replacing steam generators...But they are more cautious and hesitant to rule out potential problems that could be revealed after the new material is subjected to years of operating experience." "There's nothing to say the new Inconel 690 won't have its own particular characteristics," said Ted Marston of the Electric Power Research Institute.

One metallurgist for a U.S. vendor said his personal preference would be to stick with Inconel 600, rather than switching to Inconel 690 with less service experience.

7.0 REFERENCES

- Amar, A. S., and V. N. Shah. 1991. "Remedies for PWR Recirculating Steam Generator Tube Aging." CONF-890855-27, SMIRT-10, prepared by EG&G Idaho, Inc., Idaho Falls, Idaho.
- Aspden, R. G., T. F. Grand, and D. L. Harrod. 1989. "Corrosion Performance of Alloy 690." Presented at the Alloy 690 Workshop, New Orleans, Louisiana, April 12-14, 1989.
- Crawford, D. C., and G. S. Was. 1991. "Effect of Grain Boundary Misorientation on Intergranular Cracking of Ni-16Cr-9Fe in 360°C Argon and High Purity Water." In Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Cullen, W. H., M. J. Partridge, J. A. Gorman, and J. P. Paine. 1991. "IGA/IGSCC of Alloy 600 in Acidic Sulfate and Chloride Solutions." Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Donati, J. R., et al. 1987. "Stress Corrosion Cracking Behavior of Nickel-Base Alloys with 19% Chromium in High Temperature Water." Third International Symposium on Environmental Degradation of Materials in Nuclear Power Systems- Water Reactors, Traverse City, August 30 to September 3, 1987, pp. 697-702.
- Dow, B. L. 1991. Steam Generator Progress Report, Revision 7. Prepared by Energy Management Services, Inc., for the Electric Power Research Institute, Palo Alto, California, under Research Project S405-3.
- Esposito, J. N., G. Economy, W. A. Byers, J. B. Esposito, F. W. Pement, R. J. Jacko, and C. A. Bergmann. 1991. "Zinc Addition for Enhanced Corrosion Resistance." Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Gimond, C., P. Saint-Paul, J. Blanchet, and A. Klein. 1985. "Choix de L'Alliage 690 Pour Les tubes de Generateur de Vapeur." International Symposium, Contribution of Materials Investigations to the Resolution of Problems Encountered in PWR Plants, Fontevraud, France, p. 270.
- Gold, R. E., D. L. Harrod, R. G. Aspden, and A. J. Baum. 1990. "Alloy 690 for Steam Generator Tubing Applications." EPRI NP-6997-SD, Electric Power Institute, Palo Alto, California.
- Gras, J. M. 1991. "Stress Corrosion Cracking of Steam Generator Tubing Materials - Review and Assessment." Parkins Symposium on Fundamental Aspects of Stress Corrosion Cracking, Ed. S. M. Bruemmer, TMS Fall Meeting, TMS Warrendale, Pennsylvania.

- McIlree, A. R., T. Olberg, and J. Nestell. 1985. "Primary Side Stress Corrosion Cracking." Steam Generator Reference Book, EPRI-SGOD, Ch. 7, p. 14.
- Miglin, B. P., J. M. Sarver, D. W. Koch, K. Aoki, and H. Takamatsu. 1991. "Accelerated IGA/SCC testing of Alloy 600 in Contaminated PWR Environments." Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Miglin, B. P., and G. J. Theus. 1988. Stress Corrosion Cracking of Alloys 600 and 690 in All-Volatile-Water at Elevated Temperatures. EPRI NP-5761, Electric Power Research Institute, Palo Alto, California.
- Norrington, K., K. Stiller, and J. Nilsson. 1991. "Grain Boundary Microstructure, Chemistry, and IGSCC in Alloy 600 and Alloy 690." Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Nucleonics Week, et al. January 1990. "Outlook on Materials." Published by Nucleonics Week, Inside NRC, and Nuclearfuel, New York.
- Sakai, T., T. Senjuh, K. Aoki, T. Shigemitsu, and Y. Kishi. 1991. "Lead-Induced Stress Corrosion Cracking of Alloy 600 and 690." Fifth International Symposium on Environmental Degradation of Materials in Nuclear Power System-Water Reactors, Monterey, California.
- Santarini, G., J. Blanchet, Y. Rouillon, J. C. VanDuysen, G. Slama, and C. Gimond. 1989. "Alloy 690: Recent Corrosion Results." Presented at the Alloy 690 Workshop, New Orleans, Louisiana, April 12-14, 1989.
- Smith, K., A. Klein, P. Saint-Paul, and J. Blanchet. 1985. "Inconel 690 - A Material with Improved Corrosion Resistance for PWR Steam Generator Tubes." Proceeding of the Second International Symposium on Environmental Degradation in Nuclear Power Systems - Water Reactors, Monterey, California, p. 319. American Nuclear Society, La Grange Park, Illinois.
- Yonezawa, T., K. Onimura, N. Sasaguri, T. Kusakabe, H. Nagano, K. Yamanaka, T. Minami, and M. Inoue. 1985. "Effect of Heat Treatment on Corrosion Resistance of Alloy 690." International Symposium, Contribution of Materials Investigations to the Resolution of Problems Encountered in PWR Plants, Fontevraud, France, p. 287.

APPENDIX A

- TABLE A1. Comparison of Inconel 600 TT and Inconel 690 TT Properties
- TABLE A2. Comparison of Corrosion Resistance for Inconels 600 and 690 in Several Environments Related to PWR Primary and Secondary Environments
- TABLE A3. Trojan SG Characteristics and Status
- TABLE A4. Seabrook SG Characteristics

TABLE A1. Comparison of Inconel 600 TT and Inconel 690 TT Properties

I. Composition

Alloy 600: 76% Ni, 16% Cr, and 8% Fe.

Alloy 690 (nominal): 60% Ni, 30% Cr, and 10% Fe; C is 0.015 to 0.025%.

Chemical Composition of Alloys 600 and 690 Products Used for Caustic Stress Corrosion Tests on Fracture Mechanics-Type Specimens (Nucleonics Week, et al. 1990)									
Chemical Composition, wt%									
Material	Product	Carbon	Sulfur	Phosphorus	Silicon	Manganese	Nickel	Chromium	Iron
Alloy 600	plate, 20-mm thick	0.072	0.006	0.011	0.27	0.34	73.5	16.0	8.6
Alloy 690	bar, ϕ 100 mm	0.015	0.002	0.012	0.09	0.15	61.5	27.1	10.6

II. Thermal Treatment

Applied to enhance corrosion resistance relative to MA condition:

Alloy 600: 700°C; minimum holding time is 10 to 15 hours

Alloy 690: 704 to 732°C (1300 to 1350°F)^(a); minimum holding time is 5 to 10 hours.^(a)

III. Corrosion Characteristics

See Table A2.

IV. Wear Characteristics

Similar for Alloys 600 and 690.

V. Heat Transfer Characteristics

The thermal conductivity of Alloy 690 is estimated to be 2% to 4% lower than the Alloy 600 value in one case; laboratory data indicate an Alloy 690 thermal conductivity 8% to 9% below the Alloy 600 value (Nucleonics Week et al. 1990).

(a) Includes the range of specifications by several organizations.

VI. Mechanical Properties

	YS, ksi	UTS, ksi	Elong., %
Alloy 600, Spec. SB-163	35 min	80 min	30
Alloy 690, ^(a) Spec. SB-163	35 min	85 min	30

- (a) Laboratory testing has indicated that to reduce the potential for cracking, the yield stress for Alloy 690 TT should not exceed 56,000 psi (Amarand Shah 1991).

Tensile Properties of Alloys 600 and 690 Products Used for Caustic Stress Corrosion Tests on Fracture Mechanics-Type Specimens (Nucleonics Week, et al. 1990)								
Tensile Properties								
Material	Heat Treatment ^(a)	Room Temperature			343°C			Grain Size, ASTM
		Yield Strength, ^(b) psi	Ultimate Strength, psi	Elong., %	Yield Strength, psi	Ultimate Strength, psi	Elong., %	
Alloy 600	MA 950 to 980°C	52,200	110,000	36	42,000	98,600	35	8 to 9
	MA+HT 16 h at 700°C	50,700	107,250	37	43,500	100,000	35	id.
	SA 1150°C WQ	32,600	91,300	56	27,500	88,400	64	2 to 6 (heterogenous)
	SA+HT 16 h at 700°C	44,500	103,300	36	38,100	95,700	39	
Alloy 690	MA 1035°C	34,800	91,300	55	26,100	76,800	54	5 to 7
	MA+HT 16 h at 700°C	35,100	90,400	54	--	--	--	id.

- (a) MA = mill annealed; HT = heat treated; SA = solution annealed; and WQ = water quenched.
 (b) Laboratory testing has indicated that to reduce the potential for cracking, the yield stress for Alloy 690 TT should not exceed 56,000 psi (Amarand Shah 1991).

TABLE A2. Comparison of Corrosion Resistance for Alloys 600 and 690 in Several Environments Related to PWR Primary and Secondary Environments

	Alloy 600 MA	Alloy 600 SEN	Alloy 600 TT	Alloy 690 MA	Alloy 690 TT	Alloy 800 MA
STRESS CORROSION CRACKING:						
Acid chloride	1	(2)	1	1	1	(3-4)
Caustic below 6%	4-5	3-4	2	(1)	1	2
Caustic 10 to 15%	4	(2-3)	2	3	2	4
Pure primary and AVT water with H ₂	4	(2-3)	2-3	1	1	(1)
Alkaline sulfates	1	1	1	(1)	(1)	(1)
Acid sulfates	3	2-4	1	1	(1)	U
Sulfates plus chloride	3	3	3	1	(1)	1
Sulfur	(2-3)	(5)	1	1	1	U
Lead	4	4	U	(1)	(1)	1
INTERGRANULAR CORROSION	(3-4)	(2-3)	(2-3)	(1-2)	(1-2)	(4-5)
PITTING IN CHLORIDES	(3)	(3)	(3)	2	2	(3)
WASTAGE:						
Phosphates	(3)	U	U	(3)	U	(3)
Sulfates	(3)	(3)	(3)	(1)	U	(1)

Rankings: 1 = Best, 5 = Worst, () = Estimated, U = Unknown.

Treatments: MA = Mill Annealed, TT = Thermally Treated, SEN = Sensitized.

From EPRI Research Project S408-6, "Background Report - Alloy 690 for Steam Generator Tubing Applications," February 1990.

TABLE A3. Trojan SG Characteristics and Status

I. Characteristics

SG type: Series 51

Fabricated: 1971

Tube materials: Inconel 600 MA

Tube sheet/support plate: carbon steel

Tube sheet crevice type: tubes roll expanded and explosively expanded

Support plate crevice: drilled

Note - The Trojan SGs were initially subject to copper from heat exchangers and condensers; by 1987, all copper alloy heat exchangers had been replaced.

II. Operating Conditions

Trojan reactor operating conditions:

- Primary system temperatures: inlet is 325°C (617°F); outlet is 289°C (552°F)
- Primary system pressure: 2235 psig
- Secondary system temperature (nominal): 278°C (533°F)
- Secondary system pressure: 908 psig

Primary system water chemistry:

- Hydrogen: 15 cc/kg; 25 to 35 cc/kg
- Lithium: 0.2 to 0.5 ppm Li; 6-77 to 3-78
- Boron: 0 to 2000 ppm B as boric acid
- Silica: 1.5 ppm (initial) decreasing

Water chemistry: all volatile treatment (AVT) from start of commercial operation.

Note - Electric Power Research Institute (EPRI) water chemistry guidelines were instituted in 1988.

III. 1991 Status

Degradation mechanisms:

- U-Bend Cracking (Primary Side) - PNL examined cracked Trojan U-bend specimens under a contract with EPRI (Reference 1); all first row tubes plugged.
- Pitting - Discovered in 1982 on tube outer diameter surfaces, believed to be caused by copper.
- Denting - Not a major problem due to AVT-only water chemistry.
- Intergranular Attack (IGA)
- OD SCC at tube support plates.

Tube Plugging - In 1991, 700 tubes (17.6%) are plugged (estimated that 24% of tubes have some problem).

TABLE A4. Seabrook SG Characteristics

Characteristics

SG type: Model F.

Fabricated: 1981 in the Westinghouse Tampa facility.

Tube materials: Alloy 600 TT.

Tube sheet/support plate: 405 stainless steel.

Tube sheet crevice type: hydraulic expansion.

Support plate crevice: quatrefoil broaches (thought to have flat lands).

J-tube material: carbon steel.

Feed ring material: carbon steel.

Flow distribution baffle crevices: drilled.

Access ports: six, 6-inch ports for sludge lancing and inspection.

Design Data (from the FSAR)

Design pressure, reactor coolant side: 2485 psig.

Design pressure, steam side: 1185 psig.

Design pressure, primary to secondary: 1600 psig.

Design temperature, reactor coolant side: 650°F.

Design temperature, steam side: 600°F.

Design temperature, primary to secondary: 650°F.

Total heat transfer surface area: 55,000 ft².

Maximum moisture carry-over: 0.25 wt%.

Overall height: 67 ft, 8 in.

Number of U tubes: 5626.

U tube nominal diameter: 0.688 in.

Tube wall nominal thickness: 0.040 in.

Number of manways: 4.

Inside diameter of manways: 16 in.

Number of handholes: 6.

Design fouling factor: $0.00005 \text{ ft}^2\text{-hr-}^\circ\text{F/Btu}$.

Steam flow: $3.78 \times 10^6 \text{ lbs/hr}$.

DISTRIBUTION

No. of
Copies

No. of
Copies

OFFSITE

ONSITE

2 DOE/Office of Scientific and
Technical Information

T. Foley
Battelle - Portland Operations
500 N.E. Multnomah Avenue
Suite 650
Portland, OR 97232

10 J. Irish
Bonneville Power Administration
P.O. Box 968, MD 399
Richland, WA 99352

J.P.N. Paine
Electric Power Research Institute
P.O. Box 10412
Palo Alto, CA 94303

A. R. McIlree
Electric Power Research Institute
P.O. Box 10412
Palo Alto, CA 94303

2 J. Carter
Portland General Electric Company
Trojan Nuclear Plant
71760 Columbia River Highway
Rainier, OR 97048

J. Frewing
Portland General Electric Company
121 S.W. Salmon Street
Portland, OR 97204

DOE Richland Field Office

J. Shadel
U.S. Department of Energy
Richland Field Office
Research and Development Division
P.O. Box 550
Richland, WA 99352

28 Pacific Northwest Laboratory

S. H. Bush, MSIN K2-05
M. E. Cunningham, MSIN P8-10
J. L. Ethridge, MSIN P8-10
M. D. Freshley, MSIN P8-10
E. R. Gilbert, MSIN P8-34 (5)
R. L. Gruel, MSIN K6-46
A. B. Johnson, Jr., MSIN P8-10 (5)
R. J. Kurtz, MSIN K2-31 (5)
R. D. Orton
G. L. Tingey, MSIN P8-10
Publishing Coordination
Technical Report Files (5)

END

**DATE
FILMED
5/13/92**