CHEMICAL AND THERMAL STABILITY OF REFRIGERANT- LUBRICANT MIXTURES WITH METALS

Final Report

Dietrich F. Huttenlocher

**Spauschus Associates, Inc.
1575 Northside Drive, NW
Suite 410
Atlanta, GA 30318**

09 October 1992

Prepared for

**The Air-Conditioning and Refrigeration Technology Institute
Under
ARTI MCLR Project Number 650-50200**

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.67% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.33% of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

The U.S. Department of Energy's and the air-conditioning industry's support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared on account of work sponsored by the United States Government. Neither the United States Government, nor the Department of Energy, nor the Air-Conditioning and Refrigeration Technology Institute, nor any of their employees, nor of any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

(for journal publication submissions)

By acceptance of this article, the publisher and/or recipient acknowledges the right of the U.S. Government and the Air-Conditioning and Refrigeration Technology Institutes, Inc. (ARTI) to retain a nonexclusive, royalty-free license in and to any copyrights covering this paper.

TABLE OF CONTENTS

ABSTRACT	1
SCOPE	2
SIGNIFICANT RESULTS	3
INTRODUCTION	3
DISCUSSION OF RESULTS	5
HFC/PE Ester Mixtures	5
HFC/PAG Mixtures	7
HCFC/Hydrocarbon Lubricant Mixtures	9
CONCLUSIONS	11
TEST PROCEDURES	14
SEALED TUBE TESTS	14
EVALUATION OF AGING TESTS	14
Visual Inspection	14
Gas Chromatographic (GC) Analysis	15
Chloride and Fluoride Ion Determination	16
Oil Analysis	16
COMPLIANCE WITH AGREEMENT	18
PRINCIPAL INVESTIGATOR EFFORT	18
APPENDICES	
A - Refrigerant/Lubricant Test Data	
B - Oil Analysis Data	
C - Refrigerant and Lubricant Lists	

CHEMICAL AND THERMAL STABILITY OF REFRIGERANT-
LUBRICANT MIXTURES WITH METALS

ARTI MCLR Project Number 650-50200

Dietrich F. Huttenlocher
Spauschus Associates, Inc.
Atlanta, GA

ABSTRACT

This report presents the results of a sealed tube stability study on twenty-one refrigerant-lubricant mixtures selected from the following groupings:

- HFCs R-32, R-125, R-134, R-134a, R-143a, and R-152a with one or more lubricants selected from among three pentaerythritol esters and three polyalkylene glycols. All lubricants were carefully pre-dried to 25 ppm or less moisture content.

- HCFCs R-22, R-123, R-124, and R-142b, as well as CFC R-11, with one or more lubricants selected from among two mineral oils and one alkylbenzene fluid.

Each test mixture was aged at three temperature levels.

Primary results obtained were:

1. HFCs tested, as well as R-22, are very stable and do not undergo chemical or thermal decompositions after 14 days at temperatures up to 200°C (392°F).

2. HCFCs R-124 and R-142b have stability properties intermediate between above HFCs and the currently widely used CFC R-12.

3. HCFC R-123 while more reactive than any of the above, still offers a stability improvement by a factor of ten over R-11, the CFC refrigerant it is to replace in low pressure chiller applications.

4. All pentaerythritol ester and all polyalkylene glycol fluids showed some changes of chemical structure after exposure to 200°C (392°F), and in some cases after exposure to the lower temperatures of 150°C (300°F) and 175°C (347°F).

This report supercedes previously published quarterly reports DE/CE/23810-2A and DE/CE/23810-3A.

SCOPE

The scope of ARTI MCLR Project 650-50200 encompasses the determination of the chemical and thermal stability of twenty-one refrigerant-lubricant combinations. The test methodology chosen was the sealed tube stability test. Refrigerants and lubricants are heated at elevated temperatures in the presence of a steel catalyst. Test results are based on chemical and physical measurements designed to assess the changes that occur to the test materials during thermal aging.

Refrigerants tested as part of the project consisted of six HFCs, four HCFCs, and one CFC; the latter was only included to establish base line information. Lubricants tested were three polyglycols, three polyolesters, two mineral oils and one alkylbenzene fluid.

The goal of the project was an assessment of the general stability properties of generically selected refrigerant-lubricant mixtures, rather than endorsement (or opposite thereof) of any of the specific materials tested. Aging tests were conducted over temperatures ranging from 105°C (220°F) to 200°C (392°F) depending on the specific materials combinations tested. As it will be apparent from the results, not all materials tested perform equally well at the higher temperatures. On the other hand, not all refrigerant systems require materials capable of 200°C performance. Chemical and thermal stability of refrigerant-oil mixtures is but one of a number of properties necessary for reliable performance in refrigeration and air-conditioning systems.

SIGNIFICANT RESULTS

INTRODUCTION

A total of twenty-one refrigerant-mixtures were tested during this study. They were:

- R-22/Mineral Oil-ISO VG32 (150 SSU viscosity)
- R-32/Pentaerythritol Ester (mixed acid I)
- R-32/Polypropylene Glycol (butyl monoether)
- R-123/Mineral Oil-ISO VG32 (150 SSU viscosity)
- R-124/Alkylbenzene - ISO VG32 (150 SSU viscosity)
- R-125/Polypropylene Glycol (butyl monoether)
- R-125/Modified Polyglycol
- R-125/Pentaerythritol Ester (mixed acid I)
- R-134a/Polypropylene Glycol (butyl monoether)
- R-134a/Polypropylene Glycol Diol
- R-134a/Modified Polyglycol
- R-134a/Pentaerythritol Ester (mixed acid II)
- R-134a/Pentaerythritol Ester (mixed acid I)
- R-134a/Pentaerythritol Ester (100 cSt)
- R-142b/Alkylbenzene - ISO VG32 (150 SSU viscosity)
- R-143a/Pentaerythritol Ester (mixed acid I)
- R-152a/Alkylbenzene - ISO VG32 (150 SSU viscosity)
- R-134/Pentaerythritol Ester (mixed acid I)
- R-11/Mineral Oil-ISO VG32 (150 SSU viscosity)
- R-11/White Naphthenic Mineral Oil (ISO VG45)
- R-123/White Naphthenic Mineral Oil (ISO VG45)

Test results are presented in the form of individual data tables for each refrigerant-lubricant mixture. These tables are consolidated in Appendix A (Tables A-1 through A-21). Following each data table are the gas chromatograms for the test samples covered in each table (Figures A-1 to A-42).

Listed in the data tables is the following information:

- contents of the sealed tubes reported in each table
- aging conditions
- visual observations on sealed tube contents after aging, including change of oil (liquid phase) color expressed in units of the ASTM Standard D1500 color scale, condition of the steel catalyst, formation of insoluble materials, etc.
- chemical analysis results on aged tubes, including gas chromatography (GC) of the vapor phase tube contents, chloride

or fluoride ion content, and oil analysis results for those mixtures containing polyglycol or polyol ester lubricants: total acid number (TAN), infrared (IR) spectroscopy, and size exclusion chromatography (SEC).

Under "Chemical Analysis" the column following chloride/fluoride ion results is labelled "% Refrigerant Reacted". This value was calculated from the measured halide ion content by making the assumption that each halide ion generated equals the destruction of one refrigerant molecule. Based on past experience, this is a reasonable assumption at least at low and intermediate levels of reactivity. It is not valid for very reactive systems where more than one halide atom has been removed from refrigerant molecules.

Figures A-1 to A-42 are copies of the chromatograms obtained on the vapor content of aged sealed tubes. There are four chromatograms for each refrigerant-lubricant mixture: unused refrigerant and vapor samples aged at the three test temperatures.

Oil analysis of aged synthetic lubricants consisted of IR spectroscopy for the polyol ester samples, and SEC for the polyalkylene glycol samples. Copies of IR spectra and SEC chromatograms can be found in Appendix B (Figures B-1 to B-22).

Aged sealed tubes and their individual steel catalysts (both aged and unaged) were photographed for all test sets. Copies of photographs from those test sets that exhibited significant visual changes after aging are shown in Appendix D (Figures D-1 to D-8). Appendix D is included only with the permanently bound copies of this report.

All test materials used in this study are referred to by generic designations only. Cross references from generic to commercial designations for all lubricants tested are shown in Appendix C. Also included in Appendix C are the results of purity measurements obtained on all of the refrigerants and lubricants, as received by us. This includes GC analysis of refrigerants, and water, copper and iron content, as well as the total acid number of lubricants.

DISCUSSION OF RESULTS

Discussion of results is arranged in the order HFC/pentaerythritol (PE) ester mixtures, HFC/polyalkylene glycol (PAG) mixtures, and HCFCs.

HFC/PE Ester Mixtures

Table 1, page 6, is a summary of results taken from the individual data tables for the eight mixtures listed. The R-152a/alkylbenzene mixture has been included in this ester result table to avoid an extra classification for just one HFC/alkylbenzene mixture.

The data listed in Table 1 do not show any evidence of significant refrigerant decomposition. This holds for all test mixtures and at all aging conditions. Fluoride contents are very low and very close to the "zero" value for the test method. Values of "% Refrigerant Decomposition" for the titration blanks performed during the analyses are in the range of 0.001 to 0.002%. The actual fluoride concentrations measured (after subtraction of the titration blank) are of the same low order of magnitude.

GC analyses (Appendix A) for all Table 1 mixtures lend additional support to the above findings. Again, there is no evidence of any measurable refrigerant decomposition for any of the test mixtures.

The only changes of any significance observed with the HFC-ester mixtures are on the aged lubricants. Acid numbers of aged oils increased after all of the 200°C (392°F) tests. The increases range from 0.49 to 1.69 units (ASTM Method D664 "Test of Neutralization Number by Potentiometric Titration"). Some of the mixtures also had acid number increases at 150°C (300°F) and at 175°C (347°F). The consistent acid number increases at the highest temperature are believed to be indicative of the thermal stability limits of the fluids tested.

Reasons for the randomly occurring changes at lower temperatures are not quite apparent, except in the case of the R-134a/100 cSt ester mixture. Here, in addition to the acid number changes, IR spectral changes occurred at all test temperatures. The observed IR changes are typical of C=O absorption (formation of free acids) and C-O absorption (free alcohol functions). In addition, GC analysis of 200°C tubes (Figure A-28) detected the presence of CO₂ which is a product of the decarboxylation of ester linkages.

TABLE 1: STABILITY RESULTS HFC/PE ESTER LUBRICANTS

TEST SAMPLE	DATA TABLE	AGING TEMP. (°C)	% REFRIGERANT REACTED (calc. from F ion data)	LUBRICANT ACID NUMBER (mg KOH/g)
R-32/PE (mixed acid I)	A-2	150 (300°F) 175 (347°F) 200 (392°F)	0.002 0.001 0.001	0.00 0.00 1.67
R-125/PE (mixed acid I)	A-8	150 175 200	0.005 0.005 0.005	0.00 0.48 1.09
R-134a/PE (mixed acid II)	A-12	150 175 200	0.000 0.000 0.000	0.00 0.00 0.67
R-134a/PE (mixed acid I)	A-13	150 175 200	0.001 0.001 0.001	0.00 0.00 0.74
R-134a/PE (100 cSt)	A-14	150 175 200	0.001 0.001 0.004	0.94 0.63 0.99
Note: Aged lubricant from this mixture showed significant IR spectrum changes after aging at all temperatures.				
R-143a/PE (mixed acid I)	A-16	150 175 200	0.001 0.002 0.001	0.51 1.07 0.99
R-134/PE (mixed acid I)	A-18	150 175 200	0.001 0.000 0.000	0.59 0.83 1.69
R-152a/ALKYL- -BENZENE	A-17	150 175 200	0.000 0.001 0.000	Not applicable Not applicable Not applicable

The only other IR spectral changes observed on polyol esters were minor changes after aging at 200°C (392°F) with the R-125/PE (mixed acid I) mixture.

The overall conclusions from the HFC/PE ester tests are as follows:

1. All HFCs tested are stable at the test conditions used.

2. The high viscosity ester (100 cSt), tested with R-134a, exhibited signs of molecular changes at all three test temperatures. It is unknown at this point whether these observed changes will impact on full scale equipment performance.

3. The other two PE esters tested, mixed acid I and mixed acid II, showed little, if any, changes except for consistent increases in acid numbers after aging at 200°C (392°F). In other words, these two esters appear to be quite stable to at least 175°C (347°F).

4. All tests were performed with esters having very low moisture levels in the 25 ppm range. Results reported here may or may not be representative of the stability of PE esters in the "real world", where much higher water contents are expected to be the norm.

5. No observable reactions occurred with the R-152a/alkylbenzene mixture.

HFC/PAG Mixtures

Table 2, page 8, summarizes the test results from mixtures containing PAG lubricants. Again, there is no evidence of HFC decomposition by either GC or fluoride ion analysis under any of the three test conditions.

However, size exclusion chromatography (SEC) suggests changes occurred to the structure of the PAG molecules. This was observed to varying degrees with all three PAG lubricants tested, and at all test temperatures. As was noted under the polyol esters, the significance of these observed changes on the actual performance of the PAG lubricants is not clear at the present time. The absence of HFC decomposition products suggests that PAG molecular changes do not give rise to refrigerant instability. The most likely effects, if any, of the PAG changes would be viscosity decreases, which impact lubrication performance, and/or the formation of high molecular weight solids and sludges, which can cause systems flow restrictions.

TABLE 2: STABILITY RESULTS HFC-PAG LUBRICANTS

TEST SAMPLE	DATA TABLE	AGING TEMP. (°C)	% REFRIGERANT REACTED (calc. from F data)	Size Exclusion Chromatography
R-32/PPG BUTYL MONOETHER	A-3	150 (300°F) 175 (347°F) 200 (392°F)	0.000 0.002 0.004	Minor changes in PAG structure (all tests)
R-125/PPG BUTYL MONOETHER	A-6	150 175 200	0.001 0.002 0.002	Changes in PAG structure (all tests)
R-125/MODIFIED POLYGLYCOL	A-7	150 175 200	0.007 0.004 0.005	Changes in PAG structure (all tests)
R-134a/PPG BUTYL MONOETHER	A-9	150 175 200	0.001 0.001 0.001	Changes in PAG structure (all tests)
R-134a/PPG DIOL	A-10	150 175 200	0.000 0.001 0.000	Significant changes in PAG structure (all tests)
R-134a/MODIFIED POLYGLYCOL	A-11	150 175 200	0.001 0.001 0.001	Significant changes in PAG structure (all tests)

The test results on HFC-PAG mixtures lead to the following conclusions:

1. All HFCs tested are stable at the test conditions used.

2. Based on SEC analysis all PAGs tested exhibited varying degrees of molecular change. Again, the impact, if any, of these observed changes on full scale systems performance is unknown.

3. Also unknown at this point are the effects of moisture contents higher than the low 25 ppm level present in the test work reported here.

HCFC/Hydrocarbon Lubricant Mixtures

Table 3, page 10, summarizes the test results from the HCFC containing mixtures. It is apparent that, with the possible exception of R-22, the HCFCs tested are more reactive under the test conditions used than any of the previously discussed HFCs. Both chloride ion and vapor phase GC analyses support this contention in all cases. However, in comparison to CFCs, such as R-12, both R-124 and R-142b exhibit improved chemical and thermal stability properties. Hence, the use of these HCFCs in full scale systems should not present chemical liability questions beyond those that the industry has accepted historically with R-12 and other CFCs.

The fourth HCFC tested, R-123, is significantly more reactive than are any of the "new" refrigerants included in this project, especially at temperatures above 150°C. It must be noted, however, that R-123 is a low pressure refrigerant and will be used as a replacement for R-11 in low pressure systems. There, it will never be exposed to the higher range temperatures of the sealed tube tests.

The GC results obtained on the vapor phase contents of aged R-123 sealed tubes show the expected decomposition path for this refrigerant, namely

Unfortunately, pure samples of R-133a were not available for a quantitative calibration of GC results. All R-133a values listed in the tables are uncorrected readouts and are approximate values only.

TABLE 3: STABILITY RESULTS HCFC-HYDROCARBON LUBRICANTS

TEST SAMPLE	DATA TABLE	AGING TEMP. (°C)	% REFRIGERANT REACTED (calc. from Cl data)	GC RESULTS
R-22/Mineral Oil (ISO VG32-150 SSU)	A-1	150 (300°F) 175 (347°F) 200 (392°F)	0.001 0.003 0.004	No changes No changes No changes
R-123/Mineral Oil (ISO VG32-150 SSU)	A-4	105 (220°F) 150 160 (320°F) 175	0.045/0.032 1.56/2.71 26.0 40.5	No changes R-133a: 1.8/3.4% R-133a: 14.0% R-143a: 0.45% R-133a: 44.5% R-143a: 2.0%
R-124/Alkylbenzene (ISO VG32)	A-5	150 175 200	0.008 0.014 0.052	No changes No changes No changes
R-142b/Alkylbenzene (ISO VG32)	A-15	150 175 200	0.011 0.015 0.169	No changes No changes No measurable changes

For Comparison with Past Practices:

R-12/ Mineral Oil	175	0.2 (typical value) ⁽¹⁾	R-22
R-12/Alkylbenzene	175	0.1 (typical value) ⁽¹⁾	R-22

(1) "Sealed Tube Stability Test Results: Alternative Refrigerants"
Carrier Corporation, Syracuse, NY, September 1989

Because of the relatively limited high temperature capability of R-123, a direct comparison was established for this refrigerant with the R-11 low pressure CFC refrigerant. Table 4, page 12, summarizes the results obtained from the two refrigerants after aging at 105, 150, and 160°C (220, 300, and 320°F).

The data show that R-123 is approximately ten times more stable than is R-11. Therefore, the use of R-123 as an R-11 replacement is expected to cause fewer, if any, chemical and/or thermal stability problems than does R-11 now in equivalent applications. The reactivity of both refrigerants depends on oil quality, especially at the lower sealed tube temperatures. At 150°C (300°F) and above most, if not all, R-11 was destroyed after 14 days. In addition, all chlorine was removed from some of the R-11 molecules resulting in CO₂ formation (GC analysis). R-123 was not subject to such destructive action under the same test conditions. As a rough comparison, R-123 exhibits chemical activity at 105°C (220°F) similar to that of R-12 at 175°C (347°F).

The HCFC tests lead to the following conclusions:

1. R-22 has excellent stability, at least up to 200°C (392°F), similar to the HFCs tested under this program.
2. R-124 and R-142b are slightly more reactive than the HFCs, but are less reactive than R-12 and similar CFCs.
3. While R-123 was the most reactive new refrigerant tested during this program, it is still significantly less reactive than is R-11 - by a factor of approximately ten. Therefore, the replacement of R-11 by R-123 in low pressure refrigeration equipment will cause fewer, if any, chemical problems than may exist now.

CONCLUSIONS

The following summary conclusions can be drawn from the results reported here:

1. All HFCs tested, as well as R-22, are very stable materials and do not undergo significant chemical reactions or thermal decomposition at temperatures up to 200°C (392°F).

TABLE 4: STABILITY COMPARISON R-123 VS. R-11

TEST SAMPLE	DATA TABLE	AGING TEMP. (°C)	% REFRIGERANT REACTED (calc from C1 data)	GC RESULTS
R-123/Mineral Oil (ISO VG32)	A-4	105 (220°F) 150 (300°F) 160 (320°F)	0.045/0.032 1.56/2.71 26.0	No changes R-133a: 1.8/3.4% R-133a: 14.0%, R-143a: 0.45%
R-11/Mineral Oil (ISO VG32)	A-19	105 150 160	0.46 72.0 87.0	No measurable change R-21: 72%, R-31: <0.5% R-11: 0%, R-21: 47.8% R-31: 17.2% CO ₂ : 31.4%
R-11/White Naphthenic Oil (ISO VG46)	A-20	105 150 160	0.014 45.2 97.0	No changes R-21: 17.8%, R-31: 1.37% CO ₂ Trace R-11, R-21: 75.0%, R-31: 10.4%, CO ₂ : 13.7%
R-123/White Naphthenic Oil (ISO VG46)	A-21	105 150 160	0.002 5.84 8.85	No changes R-133a: 3.9% R-143a: 0.08% R-133a: 10.9% R-143a: 0.38% CO ₂

2. Two HCFCs tested, R-124 and R-142b, were found to be intermediate in reactivity between the above HFCs and CFCs, such as R-12.

3. While R-123 is significantly more reactive than is any of the "new" refrigerants tested here, it still offers a stability improvement by a factor of ten over R-11, the CFC refrigerant it is intended to replace in low pressure chiller applications.

4. The two low viscosity (ISO VG22 and VG32) PE esters included in the program exhibited some increases in acid number, especially after aging at 200°C (392°F). The high viscosity ester (ISO 100) tested exhibited additional evidence of molecular changes during aging. Formation of CO₂ at 200°C (392°F) indicates decarboxylation of the ester at that temperature.

5. All polyalkylene glycol lubricants exhibited some signs of molecular change after aging. The significance of these changes has not been established.

TEST PROCEDURES

SEALED TUBE TESTS

All sealed tube tests were conducted in heavy walled glass tubes, 6.35 mm I.D. and 20 cm long ($\frac{1}{4}$ " x 8") with one end sealed. After thorough cleaning with toluene and drying at 150°C (300°F) the tubes were necked 5 cm (2") from the open end. This gives finished sealed tubes with an internal free volume of 7.5-8.0 ml (about 0.5 in³).

Metal coupons were cut from valve steel (Sandvik Steel Company), 6.3 mm (1/4") wide and 32 mm (1.25") long. After cleaning with hexane the coupons were stored submerged in this solvent. One coupon was added to each tube immediately prior to necking. After necking of the tubes 1.0 ml of lubricant was added using a calibrated syringe. Refrigerant equal to the lubricant weight was next condensed from a gas handling manifold into the liquid nitrogen cooled tubes. After sealing and flame annealing of the seals the finished tubes were inspected for any visible faults. Acceptable tubes were placed into individual slots in large aluminum "blocks" of 12.7 cm (0.5") OD.

Three sealed tubes were prepared for each test set, that is, for every refrigerant-lubricant combination at each aging temperature. The aluminum blocks were heated in large convection ovens for 14 days at their respective temperatures. Oven cavities as well as internal temperatures of the blocks were monitored throughout the aging tests.

EVALUATION OF AGING TESTS

Aged sealed tubes were evaluated by combinations of the following methods:

Visual Inspection

After completion of aging sealed tubes were inspected visually. Recorded were:

- changes in color of the liquid phase scaled per ASTM Standard D1500
- appearance of insoluble reaction products, if any
- appearance of the metal coupons.

In addition, a photographic record was prepared of each test set consisting (from left to right in photograph) of a clean unused steel coupon, the aged coupon, and the sealed tube. The aged coupons for the photographs came from the GC analysis tubes. Photographs were taken as quickly as possible after opening of the tubes to minimize any effects of air oxidation on the appearance of metal surfaces, a precaution especially important for coupons from HCFC tests. Depending on the amount of chloride ion present, many of the HCFC exposed coupons corroded badly upon exposure to air.

Gas Chromatographic (GC) Analysis

All GC analyses were performed on a Gow-Mac Series 550P Thermal Conductivity Detector instrument using a Poropak "Q" column of 2.44 m (8') length. Gas samples were injected through a six-way Valco gas sample valve. Aged sealed tubes to be analyzed were connected to the gas handling manifold with a "tube breaker" assembly. After freezing of the tube contents in liquid nitrogen, the tube tips (scratched with a sharp file) were broken off. The tubes were then warmed slowly and all volatile tube contents were expanded into the manifold, which has a free volume of 1058 ml (64.4 in³). A sample of gas from this volume was injected through the sample valve into the GC column. The vapor pressure of the gas sample normally was in the 100 to 200 torr range, depending on the vapor pressure of the test refrigerant.

The column was operated under the following conditions:

Column and injector temperatures: 120°C (R-32 which eluted at 0.55-0.60 min. was also analyzed at 100°C [0.7 min peak] for better resolution of peak(s) below 0.5 min.);
 Detector temperature: 200°C; Detector current: 150 mA;
 Carrier gas: Helium; Gas flow rate: 27 ml/min;
 Sample size: 500 microliter

GC results, i.e. peak retention times, peak areas and peak heights, and area percent for each measurable peak in a chromatogram, were obtained on a Hewlett-Packard Model 3390A Integrator.

GC elution peaks of known identities are reported by their chemical designations, while those unknown to us are referred to by their peak retention times.

Chloride and Fluoride Ion Determinations

Chloride and/or fluoride ion contents of sealed tubes were determined with Orion "Ion Selective Electrodes" coupled to a Fisher "Accumet pH Ion Analyzer".

Theory predicts and past experience has shown that the chloride atoms of CFC and HCFC molecules are significantly more reactive than are their fluoride atoms. Therefore, HCFC containing mixtures were analyzed only for chloride ion content in the belief that this is a more sensitive indicator of chemical reactivity. All HFC containing mixtures were of course analyzed for fluoride ion. These determinations were performed in duplicate for every test set. All tube contents, i.e. refrigerant, lubricant, metal coupon, and all glass tube fragments were included in the halide ion determinations.

Results are reported in micrograms of halide ion. From this value we computed "% Refrigerant Reacted" based on the assumption that each halide ion found is the product of the removal of one halide atom from a refrigerant molecule. This assumption is not valid for very reactive systems, where more than one halide atom is removed from refrigerant molecules. R-123 at elevated temperature levels belongs to this latter category.

Oil Analysis

The type of analyses performed varied according to the lubricant tested, as follows:

Hydrocarbon Lubricants. Visual observations are recorded and color photographs were prepared to document the color changes of the aged fluids and the formation of decomposition products such as oil sludges, etc. This is consistent with past practices where sealed tube analysis by chemical methods has generally been confined to the analysis of refrigerants only.

Pentaerythritol Esters. The primary evaluation was the determination of acid numbers following the procedures proscribed in ASTM Method D664 "Test of Neutralization Number by Potentiometric Titration".

Where sufficient sample was available an Infrared (IR) spectrum was prepared. The spectrum of the aged oil was then compared to that of unused lubricant, shown as "Differential Spectra" in the Appendix B figures. All spectra were obtained from neat oil samples on NaCl plates.

Note: The interpretation of the IR spectra is limited to statements about gross spectral changes. A more detailed analysis requires an understanding of ester composition as well as that of potential decomposition products, which is beyond the scope of this project.

Polyalkylene Glycols. Size exclusion chromatography (SEC) was used to assess gross molecular changes of aged PAG lubricants. This technique, even more so than IR analysis, greatly benefits from detailed knowledge of the composition of the base materials and that of their potential decomposition products - again a task beyond the scope of this project.

All chromatograms were obtained using chloroform as eluent. This solvent was selected to avoid interference from residual refrigerant. The columns used were two 300 mm length sets of "Phenogel Linear Mix", with an I.D. of 2 mm. Detection was by refractive index.

COMPLIANCE WITH AGREEMENT

All work performed during this project was in full compliance with the requirements of the original Work Statement or as amended during the course of this project.

The specific changes requested by ARTI were as follows,

- (1) the substitution of R-134 for the originally proposed, but unavailable, E-134.
- (2) the addition of four sets of sealed tube stability tests involving R-11 and R-123 using the identical test protocol as defined in the work statement, except for the substitution of the 175°C aging temperature by 160°C.

PRINCIPAL INVESTIGATOR EFFORT

The principal investigator participated in the following Contract activities,

- the procurement and purity analysis of all refrigerant and lubricant samples
- scheduling and supervision of sealed tube preparation
- scheduling and supervision of analysis of aged tubes
- evaluation of test results
- preparation of monthly progress letters, abstracts for presentations at Purdue Compressor Conference and at ASHRAE/ARI Winter Meeting and Show in Chicago in January of 1993, two quarterly progress reports and the final report.

APPENDIX A

TABLE A-1: STABILITY OF R-22 WITH MINERAL OIL (150 SSU)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (0.9 G) OF TEST LUBRICANT
0.9 G OF R-22

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP, °C (°F)	VISUAL APPEARANCE OF AGED TUBES		CHEMICAL ANALYSIS		
	COLOR CHANGE OF OIL (ASTM)	OTHER VISUAL OBSERVATIONS	GC	CL ION (UG)	%R-22 REACTED
150 (300)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	2.5	0.001
175 (347)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	10.0	0.003
200 (392)	FROM 2.5 TO 3.0	DARKENING OF STEEL	NO CHANGE	16.7	0.004

FIGURE A-1

FIGURE A-2

RUN # 12 FEB/26/92 14:56:53

RT	AREA	TYPE	AR/HT	AREA%
0.34	2381	BB	0.052	0.135
1.28	1784888	PB	0.140	99.865

TOTAL AREA= 1787100
MUL FACTOR= 1.0000E+00

RUN # 16 APR/15/92 15:59:43

RT	AREA	TYPE	AR/HT	AREA%
0.33	920	BB	0.051	0.053
1.25	1730280	PB	0.139	99.947

TOTAL AREA= 1731100
MUL FACTOR= 1.0000E+00

TABLE A-2: STABILITY OF R-32 WITH PENTAERYTHRITOL
ESTER (MIXED ACID I)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-32

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-32 REACTED	OIL ACID NO.	OIL IR (DIFFERENTIAL SCAN)
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	6.0	0.002	0.00	NO SIGNIFICANT CHANGES
175 (347)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	4.7	0.001	0.00	NO SIGNIFICANT CHANGES
200 (392)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	4.2	0.001	1.67	NO SIGNIFICANT CHANGES

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-3

R-32 "As Received"

RUN # 2 FEB/19/92 08:56:24

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1063	BB	0.053	0.045	
0.60	2367700	PB	0.080	99.955	

TOTAL AREA= 2368000
MUL FACTOR= 1.0000E+00

Tube CB-01 R-32/PE Ester (mixed acid I)

14 Days @ 150°C

RUN # 3 MAR/18/92 11:06:37

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1506	BB	0.050	0.059	
0.58	2553000	PB	0.081	99.941	

TOTAL AREA= 2554500
MUL FACTOR= 1.0000E+00

FIGURE A-4

Tube CB-17
R-32/PE Ester (mixed acid I)
14 Days @ 175°C

RUN 4 MAR/18/92 11:40:26

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	0.33	1035	PB	0.038	0.040
0.58	0.58	2579000	PB	0.081	99.960

TOTAL AREA= 2580000
MUL FACTOR= 1.0000E+00

Tube CB-21
R-32/PE Ester (mixed acid I)
14 Days @ 200°C
GC Column Temp. 120°C

RUN 3 APR/01/92 09:00:36

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	0.33	1234	BB	0.048	0.051
0.58	0.58	2400000	PB	0.079	99.949

RUN 4 APR/01/92 09:13:42

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	0.33	966	BB	0.051	0.045
0.70	0.70	2141000	PB	0.088	99.955

TOTAL AREA= 2142000
MUL FACTOR= 1.0000E+00

TABLE A-3: STABILITY OF R-32 WITH POLYPROPYLENE GLYCOL (BUTYL MONOETHER)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-32

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-32 REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	NO CHANGE AT 2.0	STEEL: NO CHANGE	NO CHANGE	0.2	0.000	MINOR CHANGES IN STRUCTURE OF PAG
175 (347)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	5.4	0.002	MINOR CHANGES IN STRUCTURE
200 (392)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	14.1	0.004	MINOR CHANGES IN STRUCTURE

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-05

R-32 "As Received"

Tube CC-01 R32/PPG (butyl mono-
ether)
14 Days @ 150°C

RUN # 2 FEB/19/92 08:56:24

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1063	BB	0.053	0.045	
0.60	2367700	PB	0.080	99.955	

TOTAL AREA= 2368800
MUL FACTOR= 1.0000E+00

RUN # 2 APR/15/92 09:25:55

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1081	BB	0.045	0.043	
0.58	2527000	PB	0.080	99.957	

TOTAL AREA= 2528100
MUL FACTOR= 1.0000E+00

FIGURE A-06

Tube CC-11 R-32/PPG

14 Days @175°C

RUN 0 3 APR/15/92 10:01:40

AREA%	AREA TYPE	AR/HI	AREA%
0.33	1530 PB	0.052	0.061
0.58	2514400 PB	0.000	99.939

TOTAL AREA= 2515900
MUL FACTOR= 1.0000E+00

Tube CC-22 R32/PPG

14 Days @200°C

RUN 0 4 APR/15/92 10:31:12

AREA%	AREA TYPE	AR/HI	AREA%
0.33	1062 PB	0.049	0.047
0.58	2202100 PB	0.078	99.953

TOTAL AREA= 2203200
MUL FACTOR= 1.0000E+00

TABLE A-4: STABILITY OF R-123 WITH MINERAL OIL (ISO VG32)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
0.9 G OF R-123

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC - % OF R-123 REACTED (UNCORRECTED), PRODUCTS FOUND	CL ION (UG)	%R-123 REACTED (FROM CL ION)
105 (220)	FROM 2.5 TO 3.0	STEEL: BROWN STAIN	NO CHANGE	98.7	0.045
	FROM 2.5 TO 3.0	STEEL: BROWN	NO CHANGE	65.8	0.032
150 (300)	FROM 2.5 TO 7.0	STEEL: ETCHED	1.8 R-133A	3,260	1.56
	FROM 2.5 TO 7.5	STEEL: LIGHT SLUDGE DEPOSITS	3.4 R-133A	5,660	2.71
160 (320)	FROM 2.5 TO >8.0 (BLACK)	BLACK SLUDGE, STEEL: SLUDGE DEPOSITS	14.0 R-133A 0.45 R-143A	54,400	26.0
175 (347)	FROM 2.5 TO >8.0 (BLACK)	BLACK SLUDGE, STEEL: ETCHED, SLUDGE DEPOSITS	44.5 R-133A 2.0 R-143A	169,440	40.5

NOTE: SEE PHOTOGRAPHIC RECORD OF VISUAL OBSERVATIONS IN APPENDIX D

FIGURE A-7

R-123 "As Received"
(Base Line)

RUN 0 14 JAN/16/92 15:25:30

AREA%	RI	AREA TYPE	AM/HT	AREA%
0.34	4060	BB	0.054	0.105
9.90	2051000	BB	1.711	99.035

TOTAL AREA= 2055000
MUL FACTOR= 1.0000E+00

Tube CD-01
R-123/Mineral Oil
14days @ 105°C

RUN 0 7 FEB/19/92 10:24:04

AREA%	RI	AREA TYPE	AM/HT	AREA%
0.34	1419	BB	0.050	0.100
11.10	1207100	BB	1.423	99.092

TOTAL AREA= 1300600
MUL FACTOR= 1.0000E+00

FIGURE A-8

RUN 0 5 FEB/26/92 14:02:42

RET	AREA	TYPE	AM/III	AREA%
1.17	9670	FB	0.050	0.663
1.40	795	FB	0.102	0.054
1.70	27297	BB	0.100	1.726
10.87	1424700	BB	1.473	97.557

TOTAL AREA= 1160400
MUL FACTOR= 1.0000E100

RUN 0 7 FEB/26/92 19:42:11

RET	AREA	TYPE	AM/III	AREA%
1.01	6912	BY	0.052	0.520
1.40	1427	VB	0.053	0.111
1.70	25017	FB	0.107	2.001
1.91	2790	BB	0.202	0.216
11.26	543500	FB	0.410	42.127
17.63	709010	BB	1.355	55.010

TOTAL AREA= 1290100
MUL FACTOR= 1.0000E100

FIGURE A-7.1

R-121 "As Received"
(None listed)

RUN 0 14 JUN/18/92 15:25:30
 AREA%
 RT AREA TYPE AR/HI AREA%
 0.11 1000 BB 0.054 0.103
 9.98 3051000 BB 1.711 99.033
 TOTAL AREA= 3055000
 MIN INTENS= 1.0000E+00

Tube CD-09 R-123/Mineral
 Oil (ISO VG32)
 14 Days @ 105°C

RUN 0 6 JUN/24/92 14:39:02
 AREA%
 RT AREA TYPE AR/HI AREA%
 0.37 1044 BB 0.056 0.071
 9.78 1462400 BB 1.219 99.929
 TOTAL AREA= 1467000

FIGURE A8.1

RUN 1 2 JUN/24/92 15:23:44

AREA%	AREA	TYPE	NR/HT	AREA%
0.36	1059	FB	0.053	0.070
0.92	1724	FB	0.115	0.114
1.82	51000	BB	0.352	3.375
2.28	1457400	BB	1.222	96.441

TOTAL AREA= 1511200
MUL FACTOR= 1.0000E+00

RUN 1 2 JUL/22/92 15:34:55

AREA%	AREA	TYPE	NR/HT	AREA%
0.40	1700	BB	0.061	0.113
1.05	6777	FB	0.121	0.448
4.59	212500	FB	0.436	14.034
12.25	1293100	FB	1.449	85.405

TOTAL AREA= 1514100
MUL FACTOR= 1.0000E+00

TABLE A-5: STABILITY OF R-124 WITH ALKYL BENZENE OIL

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (0.9 G) OF TEST LUBRICANT
0.9 G OF R-124

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP, °C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC	CL ION (UG)	R-124 REACTED
150 (300)	NO CHANGE AT 2.0	STEEL: NO CHANGE	NO CHANGE	18.4	0.008
175 (347)	FROM 2.0 TO 2.5	STEEL: NO CHANGE	NO CHANGE	36.1	0.015
200 (392)	FROM 2.0 TO 3.0	STEEL: BROWN STAINS	NO MEASURABLE CHANGES	122.7	0.052

FIGURE A-9

R-124 "As Received"

RUN 0 26 JUN/17/92 15:59:17

AREA	RI	AREA TYPE	AM/HT	AREA
0.31	965	BB	0.054	0.025
2.56	3850100	PD	0.380	99.975

TOTAL AREA= 3851100
MUL FACTOR= 1.0000E+00

Tube CE-01
R-124/Alkylbenzene
14 Days @ 150°C

RUN 0 9 FEB/26/92 11:34:49

AREA	RI	AREA TYPE	AM/HT	AREA
0.31	1217	BB	0.053	0.006
2.72	1423000	PD	0.322	99.915

TOTAL AREA= 1424200
MUL FACTOR= 1.0000E+00

FIGURE A-10

RUN 10 FEB/26/92 12:19:26

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1221	BB	0.054	0.090	
2.73	1354600	PB	0.322	99.910	

TOTAL AREA= 1355900
MUL FACTOR= 1.0000E+00

Tube CE-21
R-124/Alkylbenzene
14 Days @ 200°C

RUN 5 APR/01/92 09:49:55

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1545	BB	0.051	0.111	
2.73	1386000	PB	0.323	99.889	

TOTAL AREA= 1387500
MUL FACTOR= 1.0000E+00

TABLE A-6: STABILITY OF R-125 WITH POLYPROPYLENE GLYCOL (BUTYL MONOETHER)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-125

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	R-125 REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	ELUENT AT 0.62 MIN.	1.6	0.001	CHANGES IN PAG STRUCTURE
175 (347)	NO CHANGE AT 2.5	STEEL: NO CHANGE	ELUENT AT 0.62 MIN.	3.0	0.002	CHANGES IN PAG STRUCTURE
200 (392)	NO CHANGE AT 2.5	STEEL: BLACKENED	NO CHANGE	3.1	0.002	CHANGES IN PAG STRUCTURE

(FLUORIDE ANALYSIS BLANK: 3.6)

FIGURE A-11

Tube CF-01 R-125/PPG (monobutyl-ether)

14 Days @ 150°C

STOP

RUN # 5

APR/15/92 10:48:37

AREA%

RT	AREA	TYPE	AR/HT	AREA%
0.33	1130	BB	0.049	0.069
0.62	911	BP	0.057	0.056
0.84	1626600	PB	0.100	99.847
1.22	453	BB	0.016	0.028

TOTAL AREA= 1629100

MUL FACTOR= 1.0000E+00

RUN # 25

JAN/17/92 14:49:04

AREA%

RT	AREA	TYPE	AR/HT	AREA%
0.34	3595	BB	0.050	0.106
0.83	3390200	PB	0.117	99.894
1.23	0	BB	0.000	0.000

TOTAL AREA= 3393800

MUL FACTOR= 1.0000E+00

FIGURE A-12

RUN # 6 APR/15/92 11:07:09

AREA%

RT	AREA	TYPE	NR/HIT	AREA%
0.33	4151	FB	0.050	0.256
0.62	486	PB	0.056	0.030
0.84	1618400	FB	0.100	99.696
1.22	459	PB	0.017	0.028

TOTAL AREA= 1623500
MUL FACTOR= 1.0000E+00

RUN # 11 JUN/11/92 10:11:34

AREA%

RT	AREA	TYPE	NR/HIT	AREA%
0.36	1095	FB	0.047	0.062
0.85	1773600	FB	0.097	99.751
1.21	3334	PB	0.101	0.188

TOTAL AREA= 1778100
MUL FACTOR= 1.0000E+00

TABLE A-7: STABILITY OF R-125 WITH MODIFIED POLYGLYCOL

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-125

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	R-125 REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	11.0	0.007	CHANGES IN PAG STRUCTURE
175 (347)	FROM 2.5 TO 3.5	STEEL: NO CHANGE	NO CHANGE	7.1	0.004	CHANGES IN PAG STRUCTURE
200 (392)	FROM 2.5 TO 4.0	STEEL: NO CHANGE	NO CHANGE	8.5	0.005	CHANGES IN PAG STRUCTURE

(FLUORIDE ANALYSIS BLANK: 8.2)

FIGURE A-13

FIGURE A-14

Gas Chromatograms R-125/Modified Polyglycol

TOP

UN # 20 JUL/22/92 11:04:51

RET	AREA	TYPE	AR/HT	AREA%
0.40	944	PB	0.056	0.052
1.01	1815500	PB	0.114	99.948
1.44	0	BB	0.000	0.000

TOTAL AREA= 1816500
MUL FACTOR= 1.0000E+00

STOP

RUN # 4 JUL/23/92 15:45:24

RET	AREA	TYPE	AR/HT	AREA%
0.40	1202	PB	0.065	0.065
1.04	1850100	PB	0.116	99.833
1.48	1892	BB	0.061	0.102

TOTAL AREA= 1853200
MUL FACTOR= 1.0000E+00

TABLE A-8: STABILITY OF R-125 WITH PENTAERYTHRITOL
ESTER (MIXED ACID I)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-125

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F Ion (UG)	%R-125 REACTED	OIL ACID No.	OIL IR (DIFFERENTIAL SCAN)
150 (300)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	8.2	0.005	0.00	NO SIGNIFICANT CHANGES
175 (347)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	7.7	0.005	0.48	NO SIGNIFICANT CHANGES
200 (392)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	7.7	0.005	1.09	CHANGES IN 1200-1300 CM ⁻¹ REGION

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-15

Tube CH-01

R-125/PE Ester (mixed acid I)

14 Days @ 150°C

RUN 0 9

MM/04/92 09:52:28

AREA	AREA TYPE	AM/III	AREA%
0.33	3291	0.051	0.821
0.05	1402400	0.100	99.779
1.25	0	0.000	0.000

TOTAL AREA= 1406700
MUL FACTOR= 1.0000E+00

RUN 0 25 MM/12/92 14:49:04

AREA	AREA TYPE	AM/III	AREA%
0.34	3593	0.050	0.106
0.03	3390200	0.117	99.894
1.25	0	0.000	0.000

TOTAL AREA= 3393800
MUL FACTOR= 1.0000E+00

FIGURE A 16

Tube CH-11 R-125/PE Ester (mixed acid I) Tube CH-21

14 Days @ 175°C

R-125/PE Ester (mixed acid I)

14 Days @ 200°C

RUN # 11 MAR/04/92 10:34:15

RT	AREA	TYPE	AR/HT	AREA%
0.34	1314	BB	0.054	0.000
0.87	1647800	FB	0.102	99.917
1.26	50	BB	0.002	0.003

TOTAL AREA= 1649200
MUL FACTOR= 1.0000E+00

RUN # 6 APR/01/92 10:36:21

RT	AREA	TYPE	AR/HT	AREA%
0.34	1900	BB	0.051	0.121
0.86	1569900	FB	0.101	99.879
1.24	0	BB	0.000	0.000

TOTAL AREA= 1571800
MUL FACTOR= 1.0000E+00

TABLE A-9: STABILITY OF R-134A WITH POLYPROPYLENE GLYCOL (BUTYL MONOETHER)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-134A REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	1.2	0.001	CHANGES IN PAG STRUCTURE
175 (347)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	1.2	0.001	CHANGES IN PAG STRUCTURE
200 (392)	FROM 2.5 TO 3.0	STEEL: DARKENED	NO CHANGE	1.1	0.001	CHANGES IN PAG STRUCTURE

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-17

R-134a "As Received"
(Base Line)

Tube CI-01 R134a/PPG (Butyl-
monoether)

14 Days @ 150°C

RUN 0 7 APR/15/92 11:33:09

AREA%	RT	AREA TYPE	NR/HT	AREA%
0.33	986	PB	0.049	0.056
1.07	1748900	PB	0.124	99.944

TOTAL AREA= 1748900
MUL FACTOR= 1.0000E+00

RUN 0 11 JUN/16/92 14:02:49

AREA%	RT	AREA TYPE	NR/HT	AREA%
0.34	1812	PB	0.052	0.053
1.07	2000200	PB	0.140	99.933

TOTAL AREA= 2000200
MUL FACTOR= 1.0000E+00

FIGURE A-18

Tube CI-11 R-134a/PPG (butyl monoether)

14 Days @ 175°C

Tube CI-23

14 Days @ 200°C

RUN # 8 APR/15/92 11:51:51

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.33	1229	BB	0.050	0.071
1.07	1731000	PB	0.124	99.929

TOTAL AREA= 1733000
MUL FACTOR= 0.000E+00

RUN # 12 APR/15/92 14:29:46

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.33	1226	BB	0.051	0.071
1.07	1732200	PB	0.125	99.929

TOTAL AREA= 1733400
MUL FACTOR= 1.0000E+00

TABLE A-10: STABILITY OF R-134A WITH POLYPROPYLENE GLYCOL DIOL

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	R-134A REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	NO CHANGE AT 2.0	STEEL: NO CHANGE	NO CHANGE	0.6	0.000	SIGNIFICANT CHANGES IN PAG STRUCTURE
175 (347)	NO CHANGE AT 2.0	STEEL: NO CHANGE	NO CHANGE	2.1	0.001	SIGNIFICANT CHANGES IN PAG STRUCTURE
200 (392)	FROM 2.0 TO 2.5	STEEL: NO CHANGE	NO CHANGE	0.1	0.000	SIGNIFICANT CHANGES IN PAG STRUCTURE

(FLUORIDE ANALYSIS BLANK: 8.1)

FIGURE A-19

R-134a "As Received"
(None Line) 1.00

Tube CJ-01 R-134a/Polypropylene-
glycol Diol

START 14 Days @ 150°C
0.36

1.00

STOP

RUN 0 4

JUN/24/92 13:35:10

AREA%

RT	AREA	TYPE	AR/HT	AREA%
0.36	1456	PB	0.055	0.076
1.00	1911700	PB	0.121	99.924

TOTAL AREA= 1913200
MUL FACTOR= 1.0000E+00

RUN 0 11

JUN/10/92 14:02:49

RT	AREA	TYPE	AR/HT	AREA%
0.36	1456	PB	0.055	0.076
1.00	1911700	PB	0.121	99.924

FIGURE A-20

Gas Chromatograms R-134a/Polypropyleneglycol Diol

Tube CJ-11 (14 Days @175°C)

Tube CJ-21 (14days @ 200°C)

RUN # 2 JUL/23/92 14:13:21

RT	AREA	TYPE	NR/HT	AREA%
0.40	1107	FB	0.063	0.053
1.31	2074700	FB	0.146	99.947

TOTAL AREA= 2075800
MUL FACTOR= 1.0000E+00

RUN # 5 JUN/24/92 14:04:52

RT	AREA	TYPE	NR/HT	AREA%
0.36	1227	FB	0.055	0.070
1.00	1215100	FB	0.121	99.930

TOTAL AREA= 1216400
MUL FACTOR= 1.0000E+00

TABLE A-11: STABILITY OF R-134A WITH MODIFIED POLYGLYCOL

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS			
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-134A REACTED	SIZE EXCLUSION CHROMATOGRAPHY OF OIL
150 (300)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	ELUENT AT 0.08% AT 1.0 MIN.	1.1	0.001	SIGNIFICANT CHANGES IN PAG STRUCTURE
175 (347)	FROM 2.5 TO 3.5	STEEL: NO CHANGE	0.05% AT 1.0 MIN.	2.3	0.001	SIGNIFICANT CHANGES IN PAG STRUCTURE
200 (392)	FROM 2.5 TO 4.0	STEEL: NO CHANGE	TRACE OF ELUENT AT 1.03 MIN.	2.2	0.001	SIGNIFICANT CHANGES IN PAG STRUCTURE

(FLUORIDE ANALYSIS BLANK: 8.2)

FIGURE A-21

Gas Chromatograms R-134a/Modified Polyglycol
R-134a "As Received"

Tube CK-01 (14 days @ 150°C)

RUN # 2 AUG/26/92 10:30:23

RT	AREA	TYPE	NR/HT	AREA%
0.40	837	BB	0.064	0.050
1.39	1660100	PB	0.148	99.950

TOTAL AREA= 1661000
MUL FACTOR= 1.0000E+00

RUN # 21 JUL/22/92 12:16:37

RT	AREA	TYPE	NR/HT	AREA%
0.40	1000	BB	0.063	0.040
1.03	1745	BP	0.124	0.023
1.20	2094200	PB	0.144	99.869

TOTAL AREA= 2097000
MUL FACTOR= 1.0000E+00

FIGURE A-22

Gas Chromatograms R-134a/Modified Polyglycol

RUN # 3 JUL/23/92 15:09:08

RT	AREA	TYPE	NR/HT	AREA%
0.40	1044	PB	0.056	0.049
1.31	2133200	PB	0.146	99.951

TOTAL AREA= 2134200
MUL FACTOR= 1.0000E+00

RUN # 22 JUL/22/92 13:55:16

RT	AREA	TYPE	NR/HT	AREA%
0.40	983	PB	0.057	0.049
1.03	1070	BP	0.103	0.053
1.29	2011300	PB	0.143	99.898

TOTAL AREA= 2013400
MUL FACTOR= 1.0000E+00

TABLE A-12: STABILITY OF R-134A WITH PENTAERYTHRITOL
ESTER (MIXED ACID II)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F Ion (UG)	%R-134A REACTED	OIL ACID No.	OIL IR (DIFFERENTIAL SCAN)
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	0.8	0.000	0.00	NO CHANGE
175 (347)	NO CHANGE AT 2.5	STEEL: LIGHT STAIN	NO CHANGE	0.8	0.000	0.00	NO CHANGE
200 (392)	FROM 2.5 TO 3.0	STEEL: DARKENED	NO CHANGE	0.7	0.000	0.67	NO CHANGE

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-23

R-134a "As Received"
(Base Line)

Tube CL-01; R-134a/PE Ester (mixed
acid II)

14 Days @ 150°C

STOP .33 1.07

STOP

RUN 9 APR/15/92 13:25:09

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.33	1023	BB	0.052	0.059
1.07	1749100	PB	0.125	99.942

TOTAL AREA= 1750100
NUL FACTOR= 1.0000E+00

RUN 11 JUN/16/92 14:02:49

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.34	1012	BB	0.050	0.053
1.07	2000200	PB	0.140	99.933

TOTAL AREA= 2000200
NUL FACTOR= 1.0000E+00

FIGURE A-24

Tube CL-12

R-134a/PE Ester (mixed acid II)

Tube CL-21

14 Days @ 175°C

14 Days @ 200°C

RUN # 11 APR/15/92 14:06:08

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	970	BB	0.051	0.055	
1.07	1772500	PB	0.125	99.945	

TOTAL AREA= 1773400
MUL FACTOR= 1.0000E+00

RUN # 10 APR/15/92 13:44:57

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1006	BB	0.053	0.057	
1.07	1779400	PB	0.125	99.943	

TOTAL AREA= 1780400
MUL FACTOR= 1.0000E+00

TABLE A-13: STABILITY OF R-134A WITH PENTAERYTHRITOL
ESTER (MIXED ACID I)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F Ion (UG)	%R-134A REACTED	OIL ACID No.	OIL IR (DIFFERENTIAL SCAN)
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	2.5	0.001	0.00	NO CHANGE
175 (347)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	1.4	0.001	0.00	NO CHANGE
200 (392)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	1.8	0.001	0.74	NO CHANGE

(FLUORIDE ANALYSIS BLANK: 3.1)

FIGURE A-25

Tube CM-01
R-134a/PE Ester (mixed acid I)
Acid 1.10

14 Days @ 150°C

RUN # 13

MAR/04/92 11:18:47

AREA%	AREA	TYPE	NR/111	AREA%
R1	1383	BB	0.052	0.073
9.34	1887700	PB	0.128	99.927
1.10				

TOTAL AREA= 1889100
MUL FACTOR= 1.0000E+00

RUN # 11

MAR/16/92 14:02:49

AREA%	AREA	TYPE	NR/111	AREA%
R1	1812	BB	0.052	0.065
9.34	2880200	PB	0.140	99.935
1.07				

TOTAL AREA= 2882000
MUL FACTOR= 1.0000E+00

FIGURE A-26

Tube CM-11

R-134a/PE Ester (mixed acid I)

14 Days @ 175°C

Tube CM-21

R-134a/PE Ester (mixed acid I)

14 Days @ 200°C

RUN 7 APR/01/92 11:11:11

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1273	BB	0.052	0.001	
1.10	156200	PB	0.125	99.919	

TOTAL AREA= 1563500
MUL FACTOR= 1.0000E+00

RUN 14 MAR/04/92 12:07:46

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1221	BB	0.054	0.066	
1.10	1053200	PB	0.128	99.934	

TABLE A-14: STABILITY OF R-134A WITH PENTAERYTHRITOL
ESTER (100 cST)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-134A REACTED	OIL ACID NO.	OIL IR (DIFFERENTIAL SCAN)
150 (300)	NO CHANGE AT 3.0	STEEL: NO CHANGE	NO CHANGE	1.6	0.001	0.94	SPLIT C=O AT 1700 TO 1750 CM ⁻¹
175 (347)	FROM 3.0 TO 3.5	STEEL: DARKENED	NO CHANGE	1.0	0.001	0.63	SPLIT C=O 1700 TO 1750 CM ⁻¹
200 (392)	FROM 3.0 TO 4.5	STEEL: BLACKENED	0.56% OF CO ₂ FORMED	6.8	0.004	0.99	AS ABOVE, PLUS C-O ABSORPTION AROUND 1200 CM ⁻¹

COMMENTS ON IR ANALYSIS: SPLIT CARBONYL BANDS INDICATE FORMATION OF EITHER NEW ACID MOLECULES (TRANSESTERIFICATION), OR ALDEHYDES AND KETONES, I.E. DESTRUCTION OF ESTER LINKAGES. AT 200 C ALCOHOLS ARE FORMED (C-O ABSORPTION) TOGETHER WITH THE APPEARANCE OF CO₂ (FROM GC ANALYSIS). THIS INDICATES THE BREAKAGE OF ESTER LINKAGES BY A DECARBOXYLATION MECHANISM.

FIGURE A-27

RUN 0 15 JAN/04/92 13:32:23

AREA%	RT	AREA	TYPE	AM/HT	AREA%
0.34	1014	80	80	0.051	0.053
1.10	1049000	PD	0.120		99.945

TOTAL AREA= 1050000
 MUL FACTOR= 1.0000E+00

RUN 0 11 JAN/16/92 14:02:49

AREA%	RT	AREA	TYPE	AM/HT	AREA%
0.34	1012	80	80	0.052	0.065
1.07	2000200	PD	0.140		99.935

TOTAL AREA= 2002000
 MUL FACTOR= 1.0000E+00

FIGURE A-28

Tube CN-11

R-134a/PE Ester (100 cSt)

14 Days @ 175°C

RUN # 16

MAR/04/92 14:47:44

AREA%	AREA TYPE	AR/HT	AREA%
0.34	1363 BP	0.053	0.072
1.10	1096000 PB	0.129	99.928

TOTAL AREA= 1097400
MUL FACTOR= 1.0000E+00

Tube CN-22

R134a/PE Ester (100 cSt)

14 Days @ 200°C

RUN # 8

APR/01/92 11:38:40

AREA%	AREA TYPE	AR/HT	AREA%
0.34	1627 PP	0.050	0.009
0.40	10123 PB	0.052	0.555
1.09	1011000 PB	0.127	99.356

TOTAL AREA= 1023500
MUL FACTOR= 1.0000E+00

TABLE A-15: STABILITY OF R-142B WITH ALKYL BENZENE OIL

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (0.9 G) OF TEST LUBRICANT
0.9 G OF R-142B

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP, °C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC	CL ION (UG)	R-142B REACTED
150 (300)	NO CHANGE AT 2.0	STEEL: NO CHANGE	NO CHANGE	34.8	0.011
175 (347)	FROM 2.0 TO 2.5	STEEL: SLIGHT DARKENING	NO CHANGE	45.0	0.014
200 (392)	FROM 2.0 TO 3.0	STEEL: ETCHED AND STAINED	NO MEASURABLE CHANGE	525	0.169

FIGURE A-29

R-142b "As Received"

Tube CO-02 R-142b/Alkylbenzene

14 Days @ 150°C

RUN 8 JUN/11/92 08:42:05

AREA%	RT	AREA	TYPE	NR/HT	AREA%
9.36	0.36	635	BP	0.058	0.025
0.50	0.50	555	PB	0.054	0.022
2.43	2519200	PB	0.286		99.953

TOTAL AREA= 2520400
MUL FACTOR= 1.0000E+00

RUN 9 MAR/18/92 14:45:31

AREA%	RT	AREA	TYPE	NR/HT	AREA%
0.34	1507	BP	0.052		0.082
0.48	403	PB	0.049		0.022
2.65	1829700	PB	0.313		99.896

TOTAL AREA= 1831600
MUL FACTOR= 1.0000E+00

FIGURE A-30

Tube CO-11

R-142b/Alkylbenzene

Tube CO-21

14 Days @175°C

14 Days @200°C

RUN 0 10

MAR/13/92 15:34:04

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.33	1116	BP	0.053	0.062
2.65	1799500	PO	0.314	99.938

TOTAL AREA= 1800600
MUL FACTOR= 1.0000E+00

RUN 0 17

APR/15/92 16:29:43

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.33	1034	BP	0.052	0.059
2.61	1753000	PO	0.309	99.941

TOTAL AREA= 1754000
MUL FACTOR= 1.0000E+00

TABLE A-16: STABILITY OF R-143A WITH PENTAERYTHRITOL
ESTER (MIXED ACID I)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-143A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-143A REACTED	OIL ACID NO.	OIL IR (DIFFEREN- TIAL SCAN)
150 (300)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	2.6	0.001	0.51	NO CHANGE
175 (347)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	4.1	0.002	1.07	NO CHANGE
200 (392)	FROM 2.5 TO 3.0	STEEL: BLACKENED	NO CHANGE	1.1	0.001	0.99	NO CHANGE

(FLUORIDE ANALYSIS BLANK: 3.6)

FIGURE A-31

R-143a "As Received"

RUN 0 1 FEB/19/92 08:44:18

RT	AREA	TYPE	AR/HT	AREA%
0.34	1611	BP	0.049	0.052
0.49	1064	PB	0.057	0.035
0.85	3070100	PB	0.114	99.913

TOTAL AREA= 3072000
MUL FACTOR= 1.0000E+00

Note: 0.49 min peak is probably
CO₂.

Tube CP-02
R-143a/PE Ester (mixed acid I)

RUN 0 2 MAR/18/92 13:46:21

RT	AREA	TYPE	AR/HT	AREA%
0.33	1674	BP	0.051	0.002
0.48	757	PB	0.049	0.037
0.86	2050000	PB	0.103	99.882

TOTAL AREA= 2052400
MUL FACTOR= 1.0000E+00

FIGURE A-32

Tube CP-11

R-143a/PE Ester (mixed acid I) Tube CP-21

14 Days @ 175°C

14 Days @ 200°C

RUN # 7 MAR/18/92 13:46:21

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1674	BP	0.051	0.002	
0.48	757	PB	0.049	0.037	
0.86	2050000	PB	0.103	99.002	

TOTAL AREA= 2052400
MUL FACTOR= 1.0000E+00

RUN # 13 JUN/11/92 11:09:11

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.36	4126	PV	0.053	0.189	
0.51	1024	VB	0.053	0.047	
0.86	2182000	PB	0.101	99.765	

TOTAL AREA= 2187100
MUL FACTOR= 1.0000E+00

TABLE A-17: STABILITY OF R-152A WITH ALKYL BENZENE

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (0.9 G) OF TEST LUBRICANT
0.9 G OF R-152A

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP, °C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	COLOR CHANGE OF OIL (ASTM)	OTHER VISUAL OBSERVATIONS	GC	F ION (UG)	R-152A REACTED
150 (300)	FROM 2.0 TO 2.5	STEEL: NO CHANGE	NO CHANGE	0.4	0.000
175 (347)	FROM 2.0 TO 2.5	STEEL: NO CHANGE	NO CHANGE	2.0	0.001
200 (392)	FROM 2.0 TO 3.0	STEEL: DARKENED	NO CHANGE	1.1	0.000
		(FLUORIDE ANALYSIS BLANK:		3.1)	

NOTE: R-152A AND ALKYL BENZENE LUBRICANT WERE NOT MISCIBLE AT ROOM TEMPERATURE. ALL TUBES EXHIBITED TWO DISTINCT LIQUID PHASES.

FIGURE A-33

R-152a "As Received"

Tube CQ-01; R-152a/Alkylbenzene
14 Days @ 150°C

RUN 0 10 MAR/04/92 10:22:50

RT	AREA	TYPE	AR/HT	AREA%
0.34	3322	BB	0.050	0.134
1.17	2468900	PB	0.141	99.866

TOTAL AREA= 2472300
MUL FACTOR= 1.0000E+00

RUN 0 13 APR/15/92 14:48:36

RT	AREA	TYPE	AR/HT	AREA%
0.33	930	BB	0.052	0.044
1.15	2146500	PB	0.135	99.956

TOTAL AREA= 2147500
MUL FACTOR= 1.0000E+00

FIGURE A-34

Tube CQ-12; R-152a/Alkylbenzene
14 Days @ 175°C

Tube CQ-21
14 Days @ 200°C

RUN # 14 APR/15/92 15:12:25

RT	AREA	TYPE	AR/HT	AREA%
0.33	1066	BB	0.052	0.051
1.15	2084600	PB	0.134	99.949

TOTAL AREA= 2085600
MUL FACTOR= 1.0000E+00

RUN # 15 APR/15/92 15:35:40

RT	AREA	TYPE	AR/HT	AREA%
0.33	952	BB	0.051	0.044
1.15	2170400	PB	0.135	99.956

TOTAL AREA= 2171400
MUL FACTOR= 1.0000E+00

TABLE A-18: STABILITY OF R-134 WITH PENTAERYTHRITOL
ESTER (MIXED ACID I)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
1.0 G OF R-134

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE		CHEMICAL ANALYSIS				
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL CHANGES	GC	F ION (UG)	%R-134 REACTED	OIL ACID NO.	OIL IR (DIFFEREN- TIAL SCAN)
150 (300)	NO CHANGE AT 2.5	STEEL: NO CHANGE	NO CHANGE	1.2	0.001	0.59	NO SIGNIF. CHANGES
175 (347)	FROM 2.5 TO 3.0	STEEL: NO CHANGE	NO CHANGE	0.1	0.000	0.83	NO SIGNIF. CHANGES
200 (392)	FROM 2.5 TO 3.0	STEEL: DARKENED	NO CHANGE	0.7	0.000	1.69	NO SIGNIF. CHANGES

(FLUORIDE ANALYSIS BLANK: 3.6)

FIGURE A-35

R-134 "As Received"

RUN 7 JUN/11/92 08:26:36

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.36	666	PB	0.036	0.035	
1.19	1904200	PB	0.133	99.963	

TOTAL AREA= 1904900
MUL FACTOR= 1.0000E+00

Tube CR-2 R-134/PE Ester
(mixed acid)

RUN 2 JUN/24/92 11:34:29

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.36	1210	PB	0.034	0.053	
1.21	1867600	PB	0.135	99.933	

TOTAL AREA= 1868800
MUL FACTOR= 1.0000E+00

FIGURE A-36

Gas Chromatograms of R-134/Pentaerythritol Ester (mixed acid I)

Tube CR-11 14 Days at 175°C

Tube CR-22 14 Days @ 200°C

RUN # 5 JUL/23/92 16:10:13

AREA%	RT	AREA	TYPE	NR/HT	AREA%
0.40	1070	BB	0.062	0.054	
1.49	1967900	PB	0.163	99.946	

TOTAL AREA= 1969000
MUL FACTOR= 1.0000E+00

RUN # 3 JUN/24/92 12:14:46

AREA%	RT	AREA	TYPE	NR/HT	AREA%
0.36	916	BB	0.032	0.050	
1.21	1834700	PB	0.135	99.950	

TOTAL AREA= 1835600
MUL FACTOR= 1.0000E+00

TABLE A-19: STABILITY OF R-11 WITH MINERAL OIL (ISO VG32)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
0.9 G OF R-11

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. °C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC - % OF R-11 REACTED (UNCORRECTED), PRODUCTS FOUND	CL ION (UG)	%R-11 REACTED (FROM CL ION)
105 (220)	FROM 2.5 TO 4.5	STEEL: LIGHT STAINS	NO MEASURABLE CHANGES	1,063	0.46
150 (300)	FROM 2.5 TO >8.0 (BLACK)	OIL: GELLED, STEEL: COVERED WITH SLUDGE	72.0 R-21, <0.5 R-31, 1.0 CO ₂	224,600	72.0
160 (320)	FROM 2.5 TO >8.0 (BLACK)	OIL: GELLED, STEEL: COVERED WITH SLUDGE	R-11 HAS DISAPPEARED, 47.8 R-21, 17.2 R-31, 31.4 CO ₂	270,200	87.0

NOTE: SEE PHOTOGRAPHIC RECORD OF VISUAL OBSERVATIONS IN APPENDIX D

FIGURE A-37

RUN 0 10 JUN/24/92 17:18:40

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.37	980	BB	0.057	0.053
7.85	1698000	PB	0.928	99.947

TOTAL AREA= 1698900
MUL FACTOR= 1.0000E+00

RUN 0 0 JUN/24/92 16:02:29

AREA%	RT	AREA TYPE	AR/HT	AREA%
0.36	1544	PB	0.056	0.080
7.77	1939000	PB	0.945	99.920

TOTAL AREA= 1940500
MUL FACTOR= 1.0000E+00

FIGURE A-38

RUN # 9 JUN/24/92 16:45:52

AREA%	AREA	TYPE	AR/HT	AREA%
R1				
0.37	7231	PP	0.051	1.044
0.51	94343	PB	0.055	13.624
0.89	115240	BB	0.145	16.642
5.09	315350	PB	0.463	45.539
8.57	160310	BB	0.833	23.151

TOTAL AREA= 692400
MUL FACTOR= 1.0000E+00

RUN # 4 JUL/22/92 16:32:23

AREA%	AREA	TYPE	AR/HT	AREA%
R1				
0.41	18121	PV	0.052	3.425
0.50	166110	VB	0.074	31.398
0.87	1172	BP	0.061	0.222
1.02	90938	PB	0.106	17.189
6.19	252720	BB	0.563	47.767

54541 4444 54444

TABLE A-20: STABILITY OF R-11 WITH WHITE NAPHTHENIC MINERAL OIL (ISO VG46)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
0.9 G OF R-11

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC - % OF R-11 REACTED (UNCORRECTED), PRODUCTS FOUND	CL ION (UG)	%R-11 REACTED (FROM CL ION)
105 (220)	NO CHANGE FROM 2.0	STEEL: LIGHT STAINS	NO MEASURABLE CHANGE	33	0.014
150 (300)	FROM 2.0 TO >8.0 (BLACK)	STEEL: ETCHED, LIGHT SLUDGE	17.8 R-21 1.37 R-31 CO ₂	94,500	45.2
160 (320)	FROM 2.0 TO >8.0 (BLACK)	STEEL: ETCHED, OIL: GELLED	R-11: ALMOST DISAPPEARED, 75.0 R-21 10.4 R-31 13.7 CO ₂	202,500	97.0

NOTE: SEE PHOTOGRAPHIC RECORD OF VISUAL OBSERVATIONS IN APPENDIX D

FIGURE A-39

Gas Chromatograms of R-11/White Naphthenic Mineral Oil (ISO VG46)

R-11 "As Received"

RUN # 19 JUN/24/92 17:18:40

AREA%	RT	AREA TYPE	NR/HIT	AREA%
0.37	988	BB	0.057	0.053
7.85	1698000	FB	0.928	99.947

TOTAL AREA= 1698900
MUL FACTOR= 1.0000E+00

Tube CT-01 (14 days @105°C)

RUN # 2 JUL/08/92 11:18:02

AREA%	RT	AREA TYPE	NR/HIT	AREA%
0.36	1158	BB	0.054	0.071
8.07	1622600	BB	9.958	99.929

TOTAL AREA= 1623700
MUL FACTOR= 1.0000E+00

FIGURE A-40

Gas Chromatograms of R-11/White Naphthenic Mineral Oil (ISO VG 46)

Tube CT-13 (14 days @ 150°C)

Tube CT-21 (14 days @ 160°C)

RUN # JUL/08/92 13:15:43

AREA%	RT	TYPE	AR/HT	AREA%
0.36	0.51	BP	0.054	0.081
0.51	0.89	PB	0.054	0.199
0.89	5.21	PB	0.113	1.367
5.2	8.24	PB	0.464	17.828
8.24	14:59	PB	0.940	80.524

TOT 1511700
MIN 0.0000E+00

RUN # 5 JUL/22/92 17:26:15

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.41	0.51	5906	FP	0.051	0.837
0.57	0.89	96454	PB	0.080	13.675
1.01	6.11	73669	PB	0.109	10.445
6.11	9.67	329300	PB	0.564	75.043

TOTAL AREA= 705330
MUL FACTOR= 1.0000E+00

TABLE A-21: STABILITY OF R-123 WITH WHITE NAPHTHENIC MINERAL OIL (ISO VG46)

SEALED TUBE CONTENTS:

VALVE STEEL STRIP
1.0 CC (1.0 G) OF TEST LUBRICANT
0.9 G OF R-123

AGING SCHEDULE:

14 DAYS AT TEMPERATURES SHOWN

TEST RESULTS:

AGING TEMP. C (°F)	VISUAL APPEARANCE OF TUBES		CHEMICAL ANALYSIS		
	OIL COLOR CHANGE (ASTM)	OTHER VISUAL OBSERVATIONS	GC - % OF R-123 REACTED (UNCORRECTED), PRODUCTS FOUND	CL ION (UG)	%R-123 REACTED (FROM CL ION)
105 (220)	NO CHANGE FROM 2.0	STEEL: NO CHANGE	NO CHANGE	48	0.002
150 (300)	FROM 2.0 TO 7.5	STEEL: LIGHT DEPOSITS (OIL SLUDGE)	3.9 R-133A 0.08 R-143A	12,200	5.84
160 (320)	FROM 2.5 TO >8.0 (BLACK)	STEEL: ETCHED, SLUDGE DEPOSITS	10.9 R-133A 0.38 R-133A CO ₂	37,000	8.9

NOTE: SEE PHOTOGRAPHIC RECORD OF VISUAL OBSERVATIONS IN APPENDIX D

FIGURE A-41

RUN # 14 JUN/16/92 15:23:30

AREA%	RT	AREA TYPE	AR/HIT	AREA%
0.34	4060	BB	0.034	0.103
9.98	3031000	BB	1.711	99.833

TOTAL AREA= 3035000
MIN FACTOR= 1.0000E+00

RUN # 1 JUL/08/92 10:37:20

AREA%	RT	AREA TYPE	AR/HIT	AREA%
0.36	1009	BB	0.053	0.073
10.03	1406300	BB	1.270	99.927

TOTAL AREA= 1407400
MIN FACTOR= 1.0000E+00

FIGURE A-42

PIN 0 3 JUL/00/92 11:45:43

RT	AREA	TYPE	NR/INT	AREA%
0.36	1003	BB	0.034	0.024
0.91	1170	BB	0.130	0.080
3.92	40572	FB	0.362	2.727
10.12	1418200	BB	1.273	97.069

RUN 0 23

JUL/22/92 14:36:24

RT	AREA	TYPE	NR/INT	AREA%
0.40	1056	BP	0.065	0.067
0.50	734	PB	0.062	0.047
1.05	6011	FB	0.122	0.390
4.60	171710	BB	0.434	10.866
12.15	1400700	BB	1.452	88.640

TOTAL AREA= 1580200
MUL FACTOR= 1.0000E+00

APPENDIX B

FIGURE B-01

IR Spectra of Pentaerythritol
Ester mixed acid I) aged
with R-32

- - - Unused Oil - - -

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE C-32-011	ARTI	1.	
Reference Oil	PURITY	2.	
	PHASE File on R-32	DATE 04/2/92	
	THICKNESS	OPERATOR DBR	

- - Oil aged for 14 Days at
200°C with R-32

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE C-32-011	ARTI	1.	
	PURITY	2.	
	PHASE File on R-32	DATE 0/1/92	
	THICKNESS	OPERATOR DBR	

- - Differential Scan:
Aged Oil vs. Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE C-32-011	ARTI	1.	
Differential Scan	PURITY	2.	

FIGURE B-02

Size Exclusion Chromatogram: PPG butyl monoether/R-32, 14 days @ 150°C

Polypropylene Glycol (butyl monoether) - Unused
SEC Scan in Chloroform

R-32/PPG (butyl monoether) Aged 011 150°C (Tube #CC-02)

Size Exclusion Chromatogram: PPG butyl monoether/R-32, 14 days @ 175°C

Size Exclusion Chromatograms: PPG butyl monoether/R-32, 14 days@ 200

FIGURE B-05

Size Exclusion Chromatograms
of PPG butyl monoether samples
aged with R-125.

--- 14 days at 150°C

--- 14 days at 175°C

--- 14 days at 200°C

FIGURE B-06

Size Exclusion Chromatograms
of Modified Polyglycol aged
with R-125.

--- 14 days at 150°C

--- 14 days at 175°C

--- 14 days at 200°C

FIGURE-07

IR Spectra Pentaerythritol
Ester (mixed acid I) after
Aging at 150°C with R-125.

--- Unused PE ester,
acids

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE Control Oil	ART1	1.	
Reference Oil	PURITY	2.	
	PHASE	DATE	
	THICKNESS	OPERATOR	

--- Aged PE ester,
acids

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE CR 92 OIL	ART1	1.	No discernible Changes
150°C Aged	PURITY	2.	
	PHASE	DATE	
	THICKNESS	OPERATOR	

--- Differential Scan:
Aged Oil vs. New Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE CR 92	ART1	1.	Closely balanced no
Differential Scan	PURITY	2.	significant changes
	PHASE	DATE	
	THICKNESS	OPERATOR	

FIGURE-08

IR Spectra of Pentaerythritol Ester after Aging at 200°C with R-125.

--- Unused PE ester, mixed acids I

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE Control Oil		1.	
reference Oil	PURITY	2.	
	PHASE Film on NaCl	DATE 6/2/92	
	THICKNESS	OPERATOR BHN	

--- Aged PE ester, mixed acids I

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE CR-31 OIL		1.	Some changes are noticed
	PURITY	2.	AVAR in SAN AGAR
	PHASE Film on NaCl	DATE 6/14/92	
	THICKNESS	OPERATOR BHN	

--- Differential Scan: Aged Oil vs. Unused Oil

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE CR-32 DIFF SCAN		1.	May have moderate amt.
With Control Oil BHN	PURITY	2.	of change in oil comp.
	PHASE Film on NaCl	DATE 6/15/92	
	THICKNESS	OPERATOR BHN	

FIGURE B-09

Size Exclusion Chromatograms:
PPG butyl monoether/R-134a

--- 14days at 150°C

--- 14 days at 175°C

--- 14 days at 200°C

FIGURE B-10

Size Exclusion Chromatograms: PPG Diol/R-134a, 14 days at 150°C

Polypropyleneglycol Diol - Unused Oil
SEC Scan in Chloroform

Polypropyleneglycol Diol - Aged Oil, 150°C (Tube CJ-02)

FIGURE B-11

Size Exclusion Chromatogram: PPG Diol/R-134a, 14 days at 175°C

Polypropyleneglycol Diol - Unused Oil
SEC Scan in Chloroform

Polypropyleneglycol Diol - Aged Oil, 175°C (Tube CJ-12)

FIGURE B-12

Size Exclusion Chromatograms: PPG Diol/R-134a, 14 days at 200°C

Polypropyleneglycol Diol - Unused Oil
SEC Scan in Chloroform

Polypropyleneglycol Diol - Aged Oil, 200°C (Tube C1-22)

FIGURE B-13

Size Exclusion Chromatograms: Modified Polyglycol/R-134a, 14days
at 150°C

Modified Polyglycol - Unused Oil
SEC Scan in Chloroform

Modified Polyglycol - Aged Oil, 150°C (Tube CK-02)

FIGURE B-14

Size Exclusion Chromatograms: Modified Polyglycol/R-134a, 14 days
at 175°C

Modified Polyglycol - Unused Oil
SEC Scan in Chloroform

Modified Polyglycol - Aged Oil, 150°C (Tube CK-02)

Size Exclusion Chromatograms: Modified Polyglycol/R-134a,
14 days at 200°C

Modified Polyglycol - Unused Oil
SEC Scan in Chloroform

Modified Polyglycol - Aged Oil, 200°C (Tube CK-22)

FIGURE B-16

IR Spectra: Pentaerythritol
Ester - mixed acid ~~IR~~-134a,
14 days at 200°C

- - Unused Oil

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE <u>IR-134a</u>	PURITY _____	DATE <u>1/1/52</u>	SPECTRUM NO. _____ SAMPLE _____
PHASE <u>film on NaCl</u>	THICKNESS _____	OPERATOR <u>...</u>	

- - Aged Oil, 14 days
at 200°C

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE <u>IR-134a</u>	PURITY _____	DATE <u>1/1/52</u>	SPECTRUM NO. _____ SAMPLE _____
PHASE <u>film on NaCl</u>	THICKNESS _____	OPERATOR <u>...</u>	

- - Differential Scan:
Aged oil vs. new oil

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE <u>IR-134a</u>	PURITY _____	DATE <u>1/1/52</u>	SPECTRUM NO. _____ SAMPLE _____
PHASE <u>film on NaCl</u>	THICKNESS _____	OPERATOR <u>...</u>	

FIGURE B-17

IR Spectra: Pentaerythritol
Ester - (mixed acid I)/R-134a,
14 days at 200°C

--- Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE Control RM32	ARTI	1.	
Reference Oil	PURITY	2.	
	PHASE Film on NaCl	DATE 6/2/92	
	THICKNESS	OPERATOR DBH	

SPECTRUM NO. SAMPLE

--- Aged Oil, 14 days at 200°C

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE CH 22 OIL	ARTI	1.	
	PURITY	2.	
	PHASE Film on NaCl	DATE 6/14/92	
	THICKNESS	OPERATOR DBH	

SPECTRUM NO. SAMPLE

--- Differential Scan: Aged
Oil vs. Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE CH 22 OIL	ARTI	1.	
Differential Scan	PURITY	2.	
	PHASE Film on NaCl	DATE 6/14/92	
	THICKNESS	OPERATOR DBH	

SPECTRUM NO. SAMPLE

FIGURE B-18

IR Spectra: Pentaerythritol Ester (100 cSt)/R-134a,
14 days at 150°C

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE 01001 011		1 _____	
Unused Oil	PURITY _____	2 _____	
	PHASE 111.00 Mc	DATE 5/22/52	
	THICKNESS _____	OPERATOR DAN	

SPECTRUM NO. _____
SAMPLE _____

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE 011		1 _____	
Used Oil	PURITY _____	2 _____	
Aged Oil	PHASE 111.00 Mc	DATE 5/22/52	
	THICKNESS _____	OPERATOR DAN	

SPECTRUM NO. _____
SAMPLE _____

FIGURE B-19

IR Spectra: Pentaerythritol Ester (100 cSt)/R-134a,
14 days at 200°C

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE R1001 2000 OIL	PURITY _____	1. _____	SPECTRUM NO. _____ SAMPLE _____
Unused Oil	PHASE R1001 on NaCl	2. _____	
THICKNESS _____	DATE 1/22/92	OPERATOR UNH

SPECTRUM NO. _____	ORIGIN ARTI _____	LEGEND _____	REMARKS _____
SAMPLE CR 11	PURITY _____	1. _____	SPECTRUM NO. _____ SAMPLE _____
Med 200°C	PHASE R1001 on NaCl	2. _____	
Aged Oil	DATE 1/31/92	OPERATOR DMH	
THICKNESS _____			

FIGURE B-20

IR Spectra: Differential
Scans Pentaerythritol Ester
(100 cSt)/R-134a - Aged
Oils (150°C, 175°C, 200°C)
vs. Unused Oil

- - - 150 °C

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE CH-1		1.	Note split carbonyl
Differential Scan	PURITY	2.	some unsaturation
with DMBT 3920	PHASE Film on NaCl	DATE 5/12/93	perhaps in 2nd bytone
	THICKNESS	OPERATOR DRH	at 1600-1700 cm⁻¹

- - - 175°C

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE CH-11		1.	Split carbonyl
Differential Scan	PURITY	2.	
with DMBT 3920	PHASE Film on NaCl	DATE 5/11/98	
	THICKNESS	OPERATOR DRH	

- - - 200°C

SPECTRUM NO.	ORIGIN ARTI	LEGEND	REMARKS
SAMPLE CH-12		1.	Note split carbonyl
Differential Scan	PURITY	2.	and broad C-H absorpti
with DMBT 3920	PHASE Film on NaCl	DATE 5/12/93	at 1300 cm⁻¹
	THICKNESS	OPERATOR DRH	

FIGURE B-21

IR Spectra: Pentaerythritol
Ester (mixed acid T)/R-143a
14 days at 200°C

- - Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE <u>control #32</u>	<u>ART1</u>	1. <u></u>	
<u>Reference Oil 1</u>	PURITY <u></u>	2. <u></u>	
	PHASE <u>film on NaCl</u>	DATE <u>6/3/92</u>	
	THICKNESS <u></u>	OPERATOR <u>BBB</u>	

- - Aged Oil, 14 days at 200°C

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE <u>SP 21 OIL</u>	<u>ART1</u>	1. <u></u>	
	PURITY <u></u>	2. <u></u>	
	PHASE <u>film on NaCl</u>	DATE <u>6/3/92</u>	
	THICKNESS <u></u>	OPERATOR <u>BBB</u>	

- - Differential Scan: Aged
Oil vs. Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE <u>SP 21 OIL</u>	<u>ART1</u>	1. <u></u>	<u>difference in absorbance</u>
<u>Differential Scan</u>	PURITY <u></u>	2. <u></u>	<u>reference oil</u>
	PHASE <u>film on NaCl</u>	DATE <u>6/13/92</u>	
	THICKNESS <u></u>	OPERATOR <u>BBB</u>	

FIGURE B-22

IR Spectra: Pentaerythritol
Ester- (mixed acid IYR-134,
14 days at 200°C

- - Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE Control No 12	ART1	1.	
reference oil	PURITY	2.	
	PHASE Film on NaCl	DATE 6/2/92	
	THICKNESS	OPERATOR DRB	

- - Aged Oil, 14 days at 200°C

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE cr 21 oil	ART1	1.	No discernible
200°C Aged	PURITY	2.	changes
	PHASE Film on NaCl	DATE 9/21/92	
	THICKNESS	OPERATOR DRB	

- - Differential Scan: Aged
vs. Unused Oil

SPECTRUM NO.	ORIGIN	LEGEND	REMARKS
SAMPLE cr 21	ART1	1.	Closely balanced no
Differential Scan	PURITY	2.	significant change
	PHASE Film on NaCl	DATE 9/21/92	
	THICKNESS	OPERATOR DRB	

APPENDIX C

APPENDIX C LISTS ALL TEST REFRIGERANTS AND LUBRICANTS USED IN THE COURSE OF THIS PROJECT. GENERIC DESIGNATIONS AND THEIR COMMERCIAL EQUIVALENTS ARE CROSS REFERENCED, WHERE APPLICABLE. ALSO DOCUMENTED IN APPENDIX C IS ALL INFORMATION DEVELOPED ON THE PURITY LEVEL OF THE MATERIALS USED.

TABLE C-1: TEST REFRIGERANTS

THE PURITY OF ALL REFRIGERANTS USED WAS DETERMINED BY GC ANALYSIS OF LIQUID PHASE REFRIGERANT SAMPLES. ABSENCE OF ANY MEASURABLE QUANTITIES OF CONTAMINANT GASES, EXCEPT FOR THE SMALL AMOUNTS OF "AIR" FROM INADVERTENT LEAKS IN THE GAS HANDLING SYSTEM, IS INDICATED IN THE TABLE BY THE NOTATION "PURE MATERIAL".

REFRIGERANT	GC RESULTS	REFERENCE CHROMATOGRAM
R-11	PURE MATERIAL	FIG. C-01
R-22	PURE MATERIAL	FIG. C-02
R-32	PURE MATERIAL	FIG. C-03
R-123	PURE MATERIAL	FIG. C-04
R-124	PURE MATERIAL	FIG. C-05
R-125	UNIDENTIFIED IMPURITY AT <0.5%	FIG. C-06
R-134A	PURE MATERIAL	FIG. C-07
R-134	POSSIBLE IMPURITY ELUTING AFTER R-134	FIG. C-08
R-142B	PURE MATERIAL	FIG. C-09
R-143A	CO ₂ (?) IMPURITY	FIG. C-10
R-152A	PURE MATERIAL	FIG. C-11

TABLE C-2: TEST LUBRICANTS

GENERIC IDENTIFICATION	COMMERCIAL SOURCE	COMMERCIAL DESIGNATION	TOTAL ACID No. (MG KOH/G)	WATER CONTENT (PPM)	METAL CONTENT (PPM)	
					CU	FE
MINERAL OIL (ISO VG32) - NAPHTHENIC	WITCO CHEMICAL	SUNISO 3GS	0.001	18	1	0
MINERAL OIL (ISO VG46) - NAPHTHENIC WHITE OIL	WITCO CHEMICAL	FREEZENE- NAPHTHENIC HEAVY	0.11	15	2	<1
ALKYLBENZENE	SHRIEVE CHEMICAL	ZEROL 150	<0.001	17	1	0
POLYPROPYLENE GLYCOL BUTYL-MONOETHER	ICI	EMKAROX (ISO VG32)	0.05	23#	<1	<1
MODIFIED POLY-GLYCOL (PROPRIET. COMPOSITION)	ALLIED-SIGNAL	BRL-150	0.13	21#	<1	<1
POLYPROPYLENE GLYCOL DIOL	DOW CHEMICAL	P 425 (ISO VG22)	0.07	16#	<1	<1
PENTAERYTHRITOL ESTER (MIXED ACID I)	CASTROL	ICEMATIC SW32 (ISO VG32)	0.02	24#	<1	<1
PENTAERYTHRITOL ESTER (MIXED ACID II)	ICI	EMKARATE RLE (ISO VG22)	0.08	20#	<1	<1
PENTAERYTHRITOL ESTER (100 cSt)	HENKEL-EMERY	EMERY 4078X (2928 ISO VG 100)	0.10	18#	<1	<1

= AFTER VACUUM DEHYDRATION

FIGURE C-01

Gas Chromatogram of
R-11 as Received

FIGURE C-02

Gas Chromatogram of
R-22 as Received

FIGURE C-03

Gas Chromatogram of
R-32 as received

R-32 "As Received"

RUN 8 2 FEB/19/92 08:56:24

AREA	RT	AREA TYPE	NR/HT	AREA
0.34	1063	BB	0.053	0.045
0.60	2367700	PB	0.000	99.955

TOTAL AREA= 2368800
MUL FACTOR= 1.0000E+00

FIGURE C-04

Gas Chromatogram of
R-123 as received

R-123 "As Received"
(Name Line)

RUN 8 14 JAN/10/92 15:25:30

AREA	RT	AREA TYPE	NR/HT	AREA
0.34	1063	BB	0.053	0.045
9.90	2031000	BB	1.977	99.955

INITIAL AREA= 3035000
MUL FACTOR= 1.0000E+00

FIGURE C-05

Gas Chromatogram of
R-124 as received

RUN 0 PG JUN/17/92 13:59:17

RT	AREA	TYPE	AM/MI	AREA%
10.16	3051100	PD	0.051	99.973

TOTAL AREA= 3051100
PER FACTOR= 1.0000E100

FIGURE C-06

Gas Chromatogram of
R-125 as Received

RUN 0 25 JUN/17/92 14:49:04

RT	AREA	TYPE	AM/MI	AREA%
1.25	3390200	PD	0.051	99.973

TOTAL AREA= 3390200
PER FACTOR= 1.0000E100

FIGURE C-07

Gas Chromatogram of
R-134a as Received

PRINT 0 11 JUN/16/92 14:02:49

AREA	RI	AREA TYPE	AM/HT	AREA
0.36	1012	PD	0.052	0.053
1.19	2000200	PD	0.140	99.949

PRINT AM/HT- 2000200
PRINT AM/HT- 1.0000E+00

FIGURE C-08

Gas Chromatogram of
R-134 as Received

RUN 0 7 JUN/11/92 00:26:36

AREA	RI	AREA TYPE	AM/HT	AREA
0.36	666	PD	0.036	0.035
1.19	1904200	PD	0.133	99.965

TOTAL AREA= 1904900
MUL FACTOR= 1.0000E+00

FIGURE C-09

Gas Chromatogram of
R-142b as Received

RUN 8 8 JUN/11/92 00:42:05

RT	AREA	TYPE	AR/MT	AREA2
9.36	635	BP	0.050	0.025
0.59	535	PD	0.054	0.022
2.43	2519200	PD	0.206	99.953

TOTAL AREA= 2520400
MUL FACTOR= 1.0000E+00

FIGURE C-10

Gas Chromatogram of
R-143a as Received

FIGURE C-11
Gas Chromatogram of
R-152a as Received

R-152a "As Received"

RUN 0 10 MAR/04/92 10:22:50

AREA	RI	AREA	TYPE	MR/HI	AREA
0.34	3322	88	0.050	0.134	
1.17	2468988	P8	0.141	99.866	

TOTAL AREA= 2472300
MUL FACTOR= 1.0000E+00

APPENDIX D

TABLE OF CONTENTS

APPENDIX D CONTAINS COPIES OF PHOTOGRAPHS FROM THOSE SEALED TUBE SETS THAT EXHIBITED SIGNIFICANT VISUAL CHANGES AFTER THE THERMAL AGING OF THE RESPECTIVE REFRIGERANT-OIL MIXTURES, AS FOLLOWS:

FIGURE D-1	R-123/MINERAL OIL
FIGURE D-2	R-124/ALKYLBENZENE
FIGURE D-3	R-125/MODIFIED POLYGLYCOL
FIGURE D-4	R-134A/MODIFIED POLYGLYCOL
FIGURE D-5	R-134A/PENTAERYTHRITOL ESTER (100 cSt)
FIGURE D-6	R-11/MINERAL OIL
FIGURE D-7	R-11/HEAVY NAPHTHENIC
FIGURE D-8	R-123/HEAVY NAPHTHENIC

FIGURE D-1

FIGURE D-2

FIGURE D-3

FIGURE D-4

FIGURE D-5

R-134a / PE ESTER
100 cSt

14 Days at 175°C

R-134a / PE ESTER
100 cSt

14 Days at 200°C

FIGURE D-6

R-11/Mineral Oil
ISO VG32

14 Days at 150°C

R-11/Mineral Oil
ISO VG32

FIGURE D-7

R-11/HEAVY NAPHTHENE

14 Days at 160°C

R-11/HEAVY NAPHTHENE

14 Days at 160°C

FIGURE D-8

END

DATE
FILMED

6 / 8 / 93