DECLASSIFIED

(CLASSIFICATION)

RECORDS CENTER FILE

DOUGLAS UNITED NUCLEAR, INC.

RICHLAND, WASHINGTON

DOCUMENT NO.

DUN-6463
Hanford Category C-65

SERIES AND COPY NO.

DATE

November 4, 1969

THIS DOCUMENT CONTAINS INFORMATION AS
DECLASSIFIED BY THE NATIONAL DEPARTMENT OF 1954.
ITS TRANSMITTAL OR THE DISCLOSURE OF ITS
CONTENT IS PROHIBITED.

TITLE

RECEIVED

APR 19 1983
DICHROMATE EVALUATION

OSTI

THIS MATERIAL CONTAINS INFORMATION AFFECTING
THE NATIONAL DEFENSE OF THE UNITED STATES
WITHIN THE MEANING OF THE LAWS,
TITLES 18, U.S.C., SECS. 793 AND 794, THE TRANSMISSION OR REVELATION OF WHICH IN ANY MANNER
TO AN UNAUTHORIZED PERSON IS PROHIBITED BY
LAW.

AUTHOR

P. A. Carlson

ISSUING FILE

RECEIVED

DEC 5 1969

DOUGLAS
INC.

FILE NO.
1000

THIS DOCUMENT MUST NOT BE LEFT UNATTENDED OR WHERE AN UNAUTHORIZED PERSON MAY HAVE ACCESS
TO IT. WHEN NOT IN USE, IT MUST BE STORED IN AN APPROVED LOCKED REPOSITORY WITHIN AN APPROVED
GUARDED AREA. IF IN YOUR POSSESSION AND UNDER YOUR CONTROL, YOU MUST OBTAIN A RECEIPT FROM
CLASSIFIED FILES, IN THE EVENT OF LOSS, AND ITS CONTENTS WITHIN THE LIMITS OF
THIS PROJECT AND ITS TRANSMITTAL TO, AND STORAGE AT YOUR PLACE
OF RESIDENCE IS PROHIBITED. IT IS NOT TO BE DUPLICATED. ADDITIONAL COPIES ARE REQUIRED,
OBTAIN THEM FROM THE RELATED ISSUING FILE. ALL PERSONS RECEIVING THIS DOCUMENT ARE REQUESTED
TO SIGN IN THE SPACE PROVIDED BELOW.

ROUTE TO:

PAYROLL NO.

LOCATION

FILES ROUTE
DATE

SIGNATURE AND DATE

L. H. Record

AEC-RL PROD.

57029

741 B. 12709

1-12-70

Signature

DUN RECORDS DISPOSITION

Indefinite

Destruction

Authority

B-552

Box
Bin

027037
202

DECLASSIFIED

DISTRIBUTION RESTRICTED TO U.S. ONLY

MASTER

~~SECRET~~

-1-

DUN-6463
Hanford Category C-65

GROUP 1

This document consists of
3 pages. No. 16 of
16 copies. Series A

Excluded from automatic down-
grading and declassification.

[REDACTED]

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

CLASSIFICATION CANCELLED AND CHANGED TO

Declassified

BY AUTHORITY OF RLB-CB-H

BY SE Kypdesm. 1-22-93

VERIFIED BY DC Kypdesm 1-25-93

PM Eck 1-25-93

DICHROMATE EVALUATION

P. A. Carlson

November 4, 1969

Classification not to be changed
[Signature]
Date 3-10-78

DECLASSIFIED

[Signature]
DISTRIBUTION RESTRICTED TO U.S. ONLY

DISTRIBUTION:

DATE November 4, 1969

TO R. W. Reid

FROM P. A. Carlson

SUBJECT DICHROMATE EVALUATION

1. JT Baker
2. PA Carlson
3. RG Clough, Jr.
4. AK Hardin
5. CW Kuhlman
6. AP Larrick
7. JM Lutton
8. AR Maguire
9. DW Peacock
10. JW Riches
11. JP Schmidt
12. OC Schroeder
13. JT Stringer
14. RK Wahlen
15. DUN File
16. DUN Record ✓

- References: (1) Letter, PA Carlson to AR Maguire, "Dichromate Test at KW Reactor," September 29, 1969.
- (2) DUN-5764, "PTA-176, Half-Plant Low Dichromate Evaluation at KW Reactor," AP Larrick, April 30, 1969. (Secret)

Fuel failure statistics coupled with preliminary results from the half-plant dichromate test recently completed at KW Reactor show that process water with 0.5 ppm dichromate is significantly more corrosive than process water containing 1.0 ppm dichromate with respect to localized aluminum cladding corrosion. Enough information is available, however, to indicate that the differences in terms of fuel and aluminum tube failure rates may only be operationally significant during the months of highest outlet coolant temperature operation. At lower tube outlet coolant temperatures, little difference in localized aluminum corrosion has occurred on fuels exposed to either dichromate concentration. We will be able to pin this down in better detail after the data from 36 fuel columns recently discharged from KW Reactor have been obtained and analyzed. The experience and preliminary data suggest, however, that the water chemistry variables of pH and dichromate addition should be tied to outlet coolant temperature to achieve operating economies without undue risk of fuel and/or aluminum tube failure. The following table provides interim water chemistry specifications subject to revision when the test data analysis is complete early in CY-1970.

RECOMMENDED INTERIM WATER CHEMISTRY
SPECIFICATIONS - K REACTORS

<u>Bulk Outlet Coolant Temperature</u>	<u>Maximum pH</u>	<u>Minimum Dichromate, ppm</u>
90-95	6.6	1.0
< 90	6.7	0.5
< 85	6.8	0.5

Performance And Cost Effectiveness

If an operating margin is desired, these values represent the upper (pH) and lower (dichromate) limits. They should not be exceeded except for short periods of time; i.e., one to four hours.

It should be noted that it would be preferable to tie the specification to tube outlet temperature, say to the average temperature of the 20 hottest tubes. Data from PTA-176 spans tube outlet coolant temperatures of 90-115 C and we expect to be able to narrow the requirement for 1.0 ppm dichromate water when the data analyses are complete.

The examination of the fuel columns irradiated under PTA-176 and data analysis are scheduled to be completed by January 30, 1970 at which time these specifications will be reviewed and a formal technical basis prepared for Process Standards. It should be recognized, however, that interim operation at 0.5 ppm dichromate does increase the risk of fuel failure, and that the degree of risk compared to operation with 1.0 ppm cannot be accurately assessed with available information. Fuel and Target Irradiation Technology is establishing a program of fuel examination to monitor fuel cladding corrosion behavior. Some information on the amount of corrosion as a function of fuel exposure will also be obtained from the PTA-176 data. Higher corrosion rates can be tolerated on low-exposure fuels, thus lower inhibitor concentrations can be used during periods when exposures are low.

Other uncertainties are aluminum tube and hot die size fuel behavior. We will have probolog data from KW Reactor to compare with data from KE tubes in the near future; however, this will not be indicative of localized tube corrosion. Examination of KE tubes which suffered Van Stone failures at mid-year showed no pitting of the tube walls. At this time we suggest a wait-and-see attitude and have no immediate plans to recommend aluminum tube removals for examination. With respect to hot die size fuel, we expect similar aluminum cladding localized corrosion behavior. Whether this results in equivalent failure rates remains to be shown. There could be a difference in susceptibility to pitting corrosion because the bond materials are different.

We will be working with Fuel and Target Irradiations to determine whether further testing to evaluate the effects of pH and dichromate on the behavior of hot die size fuel are warranted. In any case, these tests would not be scheduled before May 1970.

P. A. Carlson, Manager
Reactor Materials Technology

1s

DECLASSIFIED

END

DATE
FILMED

7 / 8 / 93