FY 1992 Measurements and Characterization Branch Annual Report

NREL/TP--412-5422

DE93 000094

P. C. Dippo, Editor

National Renewable Energy Laboratory
1617 Cole Boulevard
Golden, Colorado 80401-3393
Operated by Midwest Research Institute
for the U.S. Department of Energy
under Contract No. DE-AC02-83CH10093

March 1993

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

NOTICE

This report was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or any agency thereof.

Printed in the United States of America
Available from:
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Road
Springfield, VA 22161

Price: Microfiche A01
Printed Copy A03

Codes are used for pricing all publications. The code is determined by the number of pages in the publication. Information pertaining to the pricing codes can be found in the current issue of the following publications which are generally available in most libraries: *Energy Research Abstracts (ERA)*; *Government Reports Announcements and Index (GRA and I)*; *Scientific and Technical Abstract Reports (STAR)*; and publication NTIS-PR-360 available from NTIS at the above address.

DISCLAIMER

**Portions of this document may be illegible
electronic image products. Images are
produced from the best available original
document.**

TABLE OF CONTENTS

INTRODUCTION	1
Surface and Interface Analysis	1
Materials Characterization	1
Electro-Optical Characterization	1
Cell and Module Performance	2
Materials Durability and Component Reliability	2
Surface Interactions, Modification, and Stability	2
FTIR Spectroscopic and Research Center	2
HIGHLIGHTS	3
General	3
Surface and Interface Analysis	3
Materials Characterization	4
Electro-Optical Characterization	4
Photovoltaic Standards Activities	5
Cell Performance	5
Materials Durability and Component Reliability	6
Surface Interactions, Modification, and Stability	6
FTIR Spectroscopic Research Center	7
INSTRUMENTATION	9
BIBLIOGRAPHY	17
STAFF BIOGRAPHIES	23
COOPERATIVE LABORATORIES	25

INTRODUCTION

The Measurements and Characterization Branch actively supports the advancement of DOE/NREL goals for the development and implementation of the solar photovoltaic (PV) technology. The primary focus of the laboratories is to provide state-of-the-art analytical capabilities for materials and device characterization and fabrication. The branch houses a comprehensive facility that is capable of providing information on the full range of PV components. A major objective of the branch is to aggressively pursue collaborative research with other government laboratories, universities, and industrial firms for the advancement of PV technologies. Members of the branch disseminate research findings to the technical community in publications and presentations.

The Measurements and Characterization Branch encompasses seven coordinated research groups, providing integrated research and development that covers all aspects of photovoltaic materials/devices characterization.

Surface and Interface Analysis

A.J. Nelson, Senior Scientist and Group Leader
S.E. Asher, Senior Scientist
L.L. Kazmerski, Principal Scientist
H. Moutinho, Research Associate
D.W. Niles, Staff Scientist
R. Reedy, Associate Scientist
A.B. Swartlander-Franz, Associate Scientist

The work of this group entails determinations of the chemical, compositional, and microelectrical characteristics of materials, surfaces, and device interfaces with extremely high depth and spatial resolution. Techniques include secondary ion mass spectrometry (SIMS); Auger electron spectroscopy (AES); scanning Auger microscopy (SAM); X-ray photoelectron spectroscopy (XPS); electron energy loss spectroscopy (EELS); electron-stimulated desorption spectroscopy (ESD); electron-beam-induced current and voltage (EBIC and EBIV); Auger voltage contrast (AVC); high-resolution elemental and ionic mapping, including volume-indexing; cooperative soft X-ray synchrotron-source analysis; scanning tunneling microscopy (STM); and atomic force microscopy.

Materials Characterization

M.M. Al-Jassim, Senior Scientist and Group Leader
M.H. Bode, Staff Scientist
K.M. Jones, Staff Scientist
A.R. Mason, Master Technician
R.J. Matson, Staff Scientist
J. Zhu, Research Associate

This group employs advanced microscopy and microanalytical techniques in the determination of crystallographic, defect topographic, compositional, and microelectrical properties of PV materials and devices. These include electron probe microanalysis (EPMA) with energy-dispersive and wavelength-dispersive spectroscopy (EDS and WDS); scanning electron microscopy (SEM) to liquid helium temperatures; scanning transmission electron microscopy (TEM and STEM); voltage contrast; electron-beam-induced current and voltage characterization; electron diffraction; electron channeling; image analysis; X-ray diffraction; X-ray fluorescence; microcathodoluminescence; cooperative high-resolution interface analysis using high-voltage electron microscopy; and complete sample preparation facilities, including ion etching with integral SIMS analysis.

Electro-Optical Characterization

R.K. Ahrenkiel, Principal Scientist and Group Leader
D.J. Dunlavy, Associate Scientist
B.M. Keyes, Associate Scientist
D.H. Levi, Staff Scientist
C.R. Osterwald, Staff Scientist
J. Zhang, Research Associate

The work of this group involves determination of the electrical and optical properties of materials and solar cells and laser spectroscopies, including photoluminescence and specialized determinations of minority-carrier properties. Capabilities and techniques include capacitance-voltage, conductance-voltage, and temperature dependencies; Hall effect/van der Pauw measurements; laser scanning; deep-level transient spectroscopy (DLTS); photoluminescence (PL); minority-carrier lifetime (to the picosecond range) and diffusion-length measurements; determination of minority-carrier mobility by time-of-flight (TOF) measurements; picosecond laser spectroscopies; optical spectrophotometry; and ellipsometry. In addition, new facilities have been developed for the electrical characterization of high temperature superconducting materials. This includes measurements of resistance versus temperature (R vs. T), Meissner mutual inductance (MMI), and critical current.

Cell and Module Performance

K.A. Emery, Senior Scientist and Group Leader
E.E. Beck, Technician
H.R. Field, Staff Scientist
S. Rummel, Staff Scientist (PV Engineering and Applications Branch)

The work of this group includes calibrating and maintaining primary PV reference cells; performing efficiency measurements under standard reporting conditions for single and multi-junction cells and modules; calibrating secondary reference cells for the PV community; and evaluating PV device parameters. Capabilities and techniques include: (1) Current-versus-voltage measurements as a function of temperature, spectral irradiance, and concentration; (2) Spectral response as a function of temperature, voltage bias, spectral irradiance, and concentration; (3) Laser photoresponse mapping; and (4) detection of measurement-related artifacts present in other current-versus-voltage measurement systems.

Materials Durability and Component Reliability

A.W. Czanderna, Research Fellow
G.C. Herdt, Research Associate
F.J. Pern, Senior Scientist
D.E. King, Staff Scientist

The work of this group involves the testing and reliability research of advanced PV submodules and modules, with primary emphasis on PV flat-plate modules. Specific project research activities include testing and investigation of submodule and module performance, stability, energy output, and reliability lifetime characteristics, both under simulated and actual sunlight conditions. These efforts are conducted in conjunction with PV research activities originating both within and outside NREL. The group also coordinates PV thin-film module testing and reliability research for the US Department of Energy (DOE) Photovoltaic Program and develops simulated and outdoor testing methods and diagnostic techniques to understand and determine module performance and potential failure mechanisms.

Surface Interactions, Modification, and Stability

A.W. Czanderna, Research Fellow and Group Leader
G.C. Herdt, Research Associate
C.L. Fields, Visiting Professional
D.R. Jung, Research Associate
J.R. Pitts, Senior Scientist

The work of this group involves the fabrication, modification, and characterization of surfaces and interfaces to better understand their properties and structures. Capabilities include surface spectroscopies (ion scattering spectrometry (ISS), XPS, SIMS, fast atom bombardment (FAB), AES, and SAM); Fourier transform infrared spectroscopy (FTIR); and contact-angle measurements, ultramicrogravity, and quartz crystal microbalance measurements. The group is able to perform reactions in the high-pressure chamber on the LHS-10 system, or in a solar furnace. In addition, the group has experience in the preparation and characterization of polymer films and organized molecular assemblies (OMAs).

FTIR Spectroscopic and Research Center

J.D. Webb, Senior Scientist and Group Leader
D.E. King, Staff Scientist
E.J. Johnson, Research Associate

This is a Laboratory-wide service center providing Fourier-transform infrared (FTIR) spectroscopic analysis and experimental design for determination of the covalent or lattice-bonding structure of materials, the effects of chemical reactions on materials, as well as the chemical composition and sub-ppm levels of impurities or dopants in samples. Techniques include: high-resolution, mid-infrared FTIR spectroscopy in transmittance, specular reflectance, diffuse reflectance, and attenuated total reflectance (ATR) sampling modes using 5 cm², 0.5 cm², and fiber optic ATR probes, along with environmental control for in-situ analysis and measurement of reaction kinetics for most sampling modes; FT-Raman and FTIR-photoluminescence spectroscopy in the reflective mode; and FTIR microscopy for obtaining mid-infrared transmittance or reflectance spectra of sample areas as small as 10x10 μ m, and far-infrared spectroscopy (650-50 cm⁻¹) with transmittance and diffuse reflectance sample modes.

HIGHLIGHTS

General

- **R&D 100 Award** for the development of the *Atomic Processing Microscope* [APM].
- Three Branch members were honored with NREL Awards:
Brian Keyes, Outstanding Performance for "the operation of a facility which produces world class measurements characterizing semiconductor materials."
John Pern, Outstanding Achievement for "identifying the mechanisms of degradation in the ethylene vinyl acetate (EVA) copolymer used to encapsulate PV modules."
Roland Pitts, Outstanding Performance for "his work on solar induced surface transformation of materials using the solar furnace."
- More than 13,000 samples/devices/components were characterized during this past year. This included more than 46,000 measurements and tests in collaboration with some 100 organizations.

Surface and Interface Analysis

- Soft X-ray photoemission results on the H_2S gas and plasma-exposed surface of p-InP were used to correlate changes in the electronic structure to changes in the surface chemistry. These measurements indicated that the H_2S gas exposure and plasma exposure at glancing angles type-converts the p-type InP surface to an n-type surface and that the magnitude of the band bending is 0.6 eV, resulting in a homojunction interface. Additionally, for the initial H_2S exposures, the S bonds separately to both the In and the P, while at higher exposures a stable polymeric sulfur (S_n) overlayer forms. This indicates that the formation of the P-S and In-S binary compounds is diffusion limited.
- An investigation on the effects of H_2 plasma exposure of CdS using synchrotron radiation soft X-ray photoemission and optical emission spectroscopy was completed. Plasma species were identified with optical emission spectroscopy, and revealed the presence of Cd_2 and S_2 species for the respective substrates. Photoemission results indicated that exposure to the H_2 plasma preferentially removes the chalcogen component, thus creating chalcogen va-

cancies in the surface region. Additionally, the surface type converts and proceeds from a flat-band condition to a surface exhibiting band bending. The observed presence of the chalcogen vacancies and the band bending at the surface show the usefulness of plasma processing for tailoring surface electronic properties of semiconductors.

- The formation and stability of the CdS/SnO₂ interface was investigated using X-ray photoemission. In-situ photoemission measurements were acquired after each CdS deposition on SnO₂/glass to observe the development of the interface. Results show that there is minimal chemical interaction or Sn out-diffusion between the two materials. Also, the valence band offset is estimated at $1.2 \text{ eV} < \Delta E_v < 1.6 \text{ eV}$.
- A synchrotron radiation soft X-ray photoemission investigation on ZnSe/CuInSe₂ heterojunction formation was completed at the Alladin source, Synchrotron Radiation Center (SRC), University of Wisconsin-Madison. First-principles band structure calculations (S.-H. Wei and A. Zunger) show that ZnSe/CuInSe₂ has a significant valence band offset (VBO): $0.70 \pm 0.05 \text{ eV}$ for the relaxed interface and $0.60 \pm 0.05 \text{ eV}$ for the coherent interface. These large values demonstrate the failure of the "common anion rule." This is traced to a stronger Cu,d-Se, p-level repulsion in CuInSe₂ than the Zn,d-Se,p repulsion in ZnSe. ZnSe overlayers were sequentially grown in steps on p- and n-type CuInSe₂(112) crystals. RHEED analysis before and during growth indicated that the surfaces were ordered and that the ZnSe grows in registry with the substrate. In-situ photoemission measurements were acquired after each growth in order to observe changes in the valence band electronic structure as well as changes in the In 4d, Se 3d, and Zn 3d core lines. Results of these measurements reveal that the VBO is $\Delta E_v = 0.70 \pm 0.15 \text{ eV}$, in good agreement with the first-principles prediction. This work marked the fifth year of the collaboration between researchers at SRC and A.J. Nelson, Group Leader of the Surface & Interface Analysis Laboratory.
- A photoemission study of the ZnTe/CdTe heterojunction was performed with an emphasis on valence band offsets as a function of strain relaxation. A valence band offset of zero for this heterojunction would yield an ohmic back contact for PV devices. Analysis of core-level spectra during interface formation demonstrated that the ZnTe/CdTe interface was abrupt and non-reactive. The valence band offset is strain dependent and measure-

ments show that $\Delta E_v = -0.01$ eV for an unstrained interface and $\Delta E_v = 0.13$ eV for a fully strained interface.

- The surface and bulk compositions of polycrystalline CuInSe_2 thin films were determined for non-stoichiometric (non-stoichiometric means $\text{Cu/In} \neq 1$) films by XPS. Results revealed that when $\text{Cu/In} < 1$, the bulk of the thin film is a mixture of In_2Se_3 and CuInSe_2 with a skin of $\text{Cu}_3\text{In}_2\text{Se}_5$. Also, for $\text{Cu/In} > 1$, a surface skin of excess Cu mixed with CuInSe_2 was observed. The difference in the electronic structure of the surface versus the bulk of these films was further investigated using synchrotron-radiation-induced photoemission. The enhanced grain CuInSe_2 films were sputter etched (500 V Ar) and analyzed in-situ to determine core-level binding energies and Fermi level positions for the n-type CuIn_3Se_5 surface and the p-type CuInSe_2 bulk within ± 0.1 eV. The transition between the n-type surface and the p-type bulk was experimentally observed by noting the change in the position of the valence band maximum (VBM) relative to the Fermi level (E_F). From these measurements, the valence band offset (ΔE_v) between these two layers was determined to be 0.40 eV. Measurement of the work functions (ϕ) was also completed and reveals $\phi = 4.75$ eV for the CuIn_3Se_5 surface layer and $\phi = 4.04$ eV for the bulk CuInSe_2 .
- A novel method for fabricating CdS on CdTe and for passivating surface and grain boundary defects in CdTe was developed using H_2S plasma modification of CdTe at elevated temperatures.
- $\text{CdS}_x\text{Te}_{1-x}$ and $\text{ZnS}_x\text{Se}_{1-x}$ alloys were fabricated using molecular beam epitaxial (MBE) growth of CdTe and ZnSe, respectively, in an ECR H_2S plasma. Substrate temperature, gas flow, and plasma power determine the film composition (XPS analysis) and growth rate.

Materials Characterization

- Initiated and maintained collaborative programs with the silicon industry (Texas Instruments (TI), Mobil Solar, Solarex, and Crystal Systems) to characterize defects in Si. Considerable progress has been made in characterizing TI's silicon spheres. This is leading to a CRADA between TI and NREL.
- Collaborated with Solar Cells, Inc., Golden Photon, Martin Marietta, the Institute of Energy Conversion, and the in-house CdTe program on the characteriza-

tion of state-of-the-art CdTe thin-film solar cells. Transmission electron microscopy (TEM) was used to study the structural defects in these films, while SEM was used to investigate the electrical and luminescent properties of the material.

- Provided TEM characterization of hydrogen-related defects in hydrogenated polycrystalline Si.
- Collaborated with Kopin Corporation and Spire Corporation on the characterization of (GaAs/GaInP) and (GaAs/Si, InP/Si).
- New technique developments (for (a) a new EDX detector with an ultrathin Be window, allowing the detection of C and O; and (b) an on-line image analysis system using a CCD array, which allows the recording, analysis, and storage of TEM images directly from the microscope in electronic form) have been acquired and implemented.

These new attachments were installed and tested. They have significantly enhanced our characterization capabilities.

- Business development: Collaborated with Ramtron Corporation on the characterization of lead zirconate titanate (PZT) ferroelectric thin films. This collaboration resulted in an outside funding of \$86,000 during 1992 and a significant improvement of Ramtron's dynamic memory devices.

Electro-Optical Characterization

- A specially designed low-temperature photoluminescence spectroscopy system was brought on-line. Using a variable temperature cryostat combined with the optical multichannel analyzer (OMA), PL data over sample temperatures from 2 K to 300 K can be provided on a rapid turn-around basis.
- A contactless minority-carrier lifetime measurement facility was developed for industry support of crystalline silicon.
- Time-resolved photoluminescence (TRPL) was successfully used to characterize the minority-carrier lifetime of polycrystalline CdTe provided by internal and external research groups. This NREL-developed technique is being used to provide the first accurate lifetime data for these polycrystalline semiconductors, and is assisting CdTe cell research and development groups for the optimization of their cells.

- An identification of three oxygen complexes in $\text{Al}_x\text{Ga}_{1-x}\text{As}$ that are "lifetime-killer" defects was made in collaboration with the Research Triangle Institute.
- Time-resolved photoluminescence analysis of n- and p-type InP wafers supplied by the Naval Research Laboratories (NRL) indicated that the lifetime in n-type wafers is orders of magnitude larger than in comparably doped p-type wafers. These results are typical of the contributions of this technique for the qualification of material for potential cell fabrication.
- Collaborative work with Purdue University found that lifetimes in epitaxial GaAs exceeded 1.0 microsecond by enhancing the photon recycling effect. This lifetime is 27 times greater than the radiative or theoretical lifetime.
- The first results from laboratories participating in the **ASTM Cell and Module Intercomparison** were received and are currently being processed. These results are expected to be reported at the 23rd IEEE PVSC. Carl Osterwald chairs this activity.
- Revisions of ASTM draft PV standards for ASTM E44.09 (subcommittee on photovoltaics) were prepared. In conjunction with Heraeus DSET Labs, a revision of the solar weathering document was produced. This document is important to the U.S. PV program as it deals with determination of degradation of PV modules from UV exposure.

Photovoltaic Standards Activities

- The Measurements and Characterization Program was asked to lead the international intercomparison for solar cells. Carl Osterwald was appointed chair of the **PEP '93 International Intercomparison**. The first organizational meeting was held in conjunction with the 11th European Photovoltaic Solar Energy Conference in Switzerland. These international PV measurement intercomparisons are conducted about every 5 years under the direction of the Photovoltaic Energy Project (PEP). This meeting, which was attended by representatives from major international PV laboratories, established the objectives, sample set, calibration methods, and schedule for the next intercomparison. The PEP '93 Intercomparison has been scheduled to begin in July, 1993, after a second participants' meeting that will be held during the 23rd IEEE PVSC in Louisville, Kentucky. Two separate sample sets will be circulated. The first will be composed entirely of 2x2-cm single-crystal Si reference cells that each participant will calibrate with their best calibration method. The results of these calibrations will be analyzed and used to establish the World PV Scale (WPVS) of primary reference cells. The second sample set will consist of devices from newer PV technologies that have unique measurement problems, such as narrow band-gap cells, large-area cells, and series-connected tandem cells. Each participant is free to use whatever methods are appropriate to measure the second sample set.
- A new standardized outdoor I-V system for evaluating the wide variety of PV cells and modules under natural sunlight has been built. The system is designed to cover the current range from $\pm 10 \mu\text{A}$ to $\pm 40 \text{ A}$ and a voltage range from $\pm 0.001 \text{ V}$ to $\pm 100 \text{ V}$. The system can bias in either direction and is designed to identify bias related artifacts. The system also measures the spectral irradiance, air temperature, sample temperature, wind speed, humidity, and direct and diffuse irradiance. In addition, the system is capable of biasing over a user-defined range.
- A new outdoor I-V system for comparing rating methods for crystalline and thin-film technologies has been completed and is currently performing data acquisition at NREL on crystalline Si, CIS, a-Si, and CdTe modules. The system can perform I-V measurements of 16 modules at 1-minute intervals versus air temperature, sample temperature, wind speed, humidity, direct and diffuse irradiance, and spectra. The system was developed to allow the comparison of all the various module rating methods at the same site and time interval with all relevant PV technologies.
- The large-area pulsed solar simulator (LAPSS) data acquisition system has been modified to handle high capacitance modules using a capacitive sweep circuit with varying sweep duration and the ability to measure the current at a fixed power supply voltage. The safety of the LAPSS system has been improved by incorporating a new HV cable with interlocks supplied by the manufacturer as a result of an informal suggestion during the Tiger Team visit. The high intensity lamp housing for the pulsed solar simulator has been installed.

Cell Performance

- The Spectrolab X25 continuous solar simulator, used for standardized single and multi-junction cell and submodule measurements and calibration, has been upgraded to accommodate 0.3 m² single and multi-junction modules.
- In support of internal research, subcontracted research, PV manufacturers, and the PV community, 1054 spectral response measurements, 1339 cell I-V calibrations, and 1931 module measurements were performed. These measurements/calibrations give the entire PV community a calibration traceability path to NREL. US manufacturers use this calibration traceability for their quality control programs.
- Procedures were developed for polymer thin film sample preparation techniques, test methods, and numeric analysis, and experiments were conducted for developing and ranking new formulations and new encapsulation materials with various UV absorbers, anti-oxidants, and UV-absorbing glass superstrates.
- Development of procedures, techniques, and test methods for the diagnostic analysis of weather-degraded PV modules was continued (including non-destructive hot-spot infrared imaging, isolation of individual solar cells, resistances, and dark I-V measurements of the isolated solar cells, and destructive EVA sampling and compositional analysis). The analysis was completed for a large number of degraded EVA films sampled from various modules made by several PV manufacturers. The results show that EVA degradation and discoloration result primarily from the loss of Cyasorb UV 531 and the formation of long conjugated C=C bonds due to loss of acetate pendant groups.

Materials Durability and Component Reliability

- The broad-based applications potential has been elucidated for using fluorescence analysis (FA) to monitor or establish (1) the extent of ethylene vinyl acetate (EVA) discoloration and degradation in field-deployed PV modules, (2) the extent of discoloration of other PV encapsulant polymers, (3) the relative number of residual chromophores in EVA at various stages of processing, and (4) an understanding of structural changes occurring within polymers that produce discoloration. The FA was also used to assist other researchers at NREL for solution-grown CdS thin films, porous Si, and electrochromic samples.
- Degradation mechanisms of EVA encapsulant films have been identified via various acceleration experiments. The key thermal and photothermal EVA discoloration from polyene formation and color reversal by photobleaching are competing processes during the photothermal degradation process, and photobleaching of the discolored EVA can be effected by both the UV and visible light in the presence of air.
- The effects of EVA yellowing/browning on the I-V and efficiency of the solar cells were quantified in a degradation study of various EVA-encapsulated solar cells under accelerated thermal and photothermal conditions. The results further support previously established conclusions that UV exposure, elevated temperature, and hermetic enclosure are three major EVA-browning factors.
- The degradation mechanisms of PVB encapsulants in weathered PV modules are similar to those for EVA, as shown by FA and other techniques.
- Studies were initiated on the formation mechanisms of SnO₂/CdS interfaces and their stability in real environments. Modules that were degraded by water vapor have been acquired for analysis by surface analysis techniques.
- The purchase, installation, and testing were completed for three light sources, including a DSET Suntest CPS table-top exposure system, an Oriel 1-kW Xe arc lamp light source, and an Oriel 1-kW Xe arc lamp UV-enhanced solar simulator, resulting in a greatly improved capability and capacity of performing accelerated photodegradation experiments. The purchase, installation, and testing were completed for the hardware, computer system, and software of an HP Model 1090/M high performance liquid chromatograph (HPLC) and a SPEX Model FL112 fluorescence spectrophotometer.
- Practical suggestions were made to staff members of several PV manufacturers for improving the current EVA formulations and processing conditions, on the basis of NREL accumulated experimental results and observations.

Surface Interactions, Modification, and Stability

- A number of experiments in rapid thermal processing at the NREL High Flux Solar Furnace were carried out. These included processing of ceramic super-

conductors, the growth of diamond-like carbon films, metallization and joining of engineered ceramic materials, and cladding of cermet powders to stainless steel.

- NREL CRADA #5 was initiated with Brush Wellman, Inc., in June, 1992. Work has proceeded on schedule for new methods of metallizing and bonding engineered ceramic materials. Negotiations for extending the CRADA into a second phase of development are underway. Contributions were made to the development of the Coors CRADA and planning of experiments to elucidate the growth mechanism of SiC on SiO₂ surfaces in the high-flux solar environment.
- Patent disclosures were filed on three promising technologies. The applications are in various stages of preparation: "Rapid Thermal Metalorganic Deposition of Metal and Oxide Thin Films," NREL IR#92-10, DOE Case No. S-75,895; "Solar-Induced Chemical Vapor Deposition (CVD) of Diamond-Type Carbon Films," NREL IR#92-27; and "Modification of Aerodynamic Surfaces to Minimize Soil Retention," NREL IR#92-22.
- In studies of copper deposited onto the organic functional end group of organized molecular assemblies (OMAs), we used XPS to show that Cu interacts with the OH groups of 11-mercaptoundecanol for coverages below 0.5 nm. At higher coverages, copper penetrates the OMA and reaches the OMA/Au interface. For Cu deposited onto OMAs with a CN end group, weak interactions occur below 0.1 nm; then further deposition of copper resides primarily at the OMA/Au interface.
- A critical review of research needs and opportunities in surface processing was completed and addresses 10 topical areas of applied surface science. Six of the topical areas (i.e., corrosion, polymer/metal (oxide) interfaces, thin-film multilayer solar collectors, accelerated life testing, interfacial microchemical characterization, and organized molecular assemblies) are directly relevant to PV devices. The other topics covered were fuel cells and solid batteries, lubrication and wear surfaces, photoelectrochemistry, and conducting polymers.
- The proceedings of a surface processing workshop were edited, published as an NREL document [24], and accepted for publication in Critical Reviews in Surface Chemistry. The 440-page NREL document contains current status summaries of methods of

surface characterization, surface modification, and the recommendations of research needs and opportunities in 10 topical areas of applied surface science (see previous bullet).

- An invention disclosure was made for using OMAs on high surface area materials as selective molecular getters.
- A collaborative study is now in progress with the University of Denver using their O-Atom Beam Facility to expose surfaces for XPS, FTIR, and ISS analysis at NREL. Initial results have been obtained after exposing Ag films to the ground-state, ca. 5-eV, O-atom source and for several silicone polymers.
- The adsorption of toluene and trichloroethylene (TCE) and the competitive adsorption of water on several different polymers has been investigated using beam microbalance techniques. Polycarbonate coated onto high-area silica gels is the best polymer of those used for adsorbing TCE.

FTIR Spectroscopic Research Center

- Room-temperature photoluminescence (PL) spectra were obtained from crystalline Si, GeGaAs, CuInSe₂, and GaInAsP using the Nicolet 800 FTIR spectrophotometer with an FT-Raman accessory. This new measurement technique enhances our capability to measure PL in the infrared, and will enable sensitive, convenient characterization of these materials.
- We contributed to a detailed study of differences in hydrogen evolution rate from annealed, hydrogenated amorphous silicon samples prepared using different deposition methods. The results contributed to better understanding of structural differences between these materials.
- Under our work-for-others contract with NASA through SAIC, we published a paper describing the interactions between contaminants in the composite materials used to prepare solid rocket motors.

INSTRUMENTATION

SURFACE AND INTERFACE ANALYSIS LABORATORY

Instrument	Range/Capacity	Unique Features and Uses
XPS/Auger System (Perkin Elmer PHI 550)	2-mm spot size detection sensitivity of 0.1 at. % Li to U, 1-cm ² sample size	Performs AES, XPS, UPS, EELS in conjunction with depth profiling quantitative elemental analysis and chemical bonding information, angle resolved photoemission.
Scanning Auger Microprobe (Perkin-Elmer PHI 590)	0.1- μ m spot size, SAM detection sensitivity of 0.1 at. % for Li to U, SIMS detection of 1 ppm for H to U, 1-cm ² sample size	Performs SAM and SIMS analysis with depth profiling, quantitative elemental analysis, and surface compositional maps, up to (5000X micrographs of surface features).
Scanning Auger Microprobe (Perkin-Elmer PHI 600)	0.02- μ m spot size, same detection sensitivities as for PHI 590 1-cm ² sample size	Performs SAMS and SIMS analysis with depth profiling quantitative elemental analysis and surface compositional maps, (up to 50,000X micrographs of surface features). Hot/cold stage.
Ion Microprobes (Cameca IMS-3f)	10-200- μ m beam spot: Cs, O, or Ar primary ions; all elements and isotopes, H-U, sensitivities of 1 ppm-1 ppb: 1-cm ² sample size	Performs high-sensitivity profiling and mass scans with 10-nm depth resolution; mass resolution ($M\Delta/M$) = 10,000 lateral ion imaging resolution of 1 μ m.
Scanning Tunneling Microscope (RHK 100 and McAllister)	Atomic-level spatial resolution	Nanometer through atomic level imaging of conducting samples; light bias for higher resistivity semiconductors; ultrahigh vacuum chamber; sample and tip exchange.
Atomic Processing Microscope (APM)	Atomic-level spatial resolution; spectroscopic imaging	STM capabilities for spectroscopic imaging; atomic and nanoscale processing, including single-atom manipulation; nanoscale characterization.
Scanning Tunneling Microscope/ Atomic Force Microscope (Park Scientific)	Atomic-level spatial resolution	Ultrahigh vacuum STM and AFM capabilities.
Scanning Force Microscope (Park Scientific AutoProbe)	Contact and non-contact imaging on nanometer scale	Air-operated atomic force microscope for the nanoscale characterization of non-conducting surfaces, including biological samples.

MATERIALS CHARACTERIZATION GROUP

Instrument	Range/Capacity	Unique Features and Uses
Electron probe X-ray microanalyzer (EPMA) Cameca-MBX	EDS and WDS analysis of an accuracy of $\pm 0.5\%$	Quantitative compositional analysis of all elements heavier than boron.
SEM JEOL JSM-35C	1-49-kV, secondary electron imaging (SEI) 5-nm resolution back-scattered electronic imaging (BEI) 9-nm resolution	EDS: compositional analysis ($>Na$); EC: Crystalline type orientation and quality; EBIC: Microcharacterization of the electrical activity of electronic materials, junction location, and diffusion length measurement.
SEM JEOL JSM-840	0.2-40-kV, liquid -helium cathodoluminescence (CL) cold stage. Integrated and spectral CL from $10^{\circ}C$ to RT° , from 300 nm to 1.8 μm	Characterize relative impurity concentrations, defect densities and distributions, bandgap (E_g), and sub-bandgap (defect) luminescence with high resolution and correlation with topography.
TEM Philips CM - 30	KeV: 300, resolution: 2.3 $\text{\AA}$, Tilt: $\pm 60^{\circ}$	Performs structural, analytical, and high resolution examination of a wide range of materials.

ELECTRO-OPTICAL CHARACTERIZATION LABORATORY

Instrument	Range/Capacity	Unique Features and Uses
Photoluminescence Spectroscopy System	CW and cavity-dumped (40 kHz to 40 MHz) excitation sources, detection capability from 400 to 1,700 nm, sample temperature range of 4 to 310 K	Energy-resolved photoluminescence spectroscopy.
Photoluminescence Lifetime System	Cavity-dumped (40 KHz to 40 MHz) excitation, detection capability from 700 to 1,700 nm, 50-ps time resolution, sample temperature range of 4 to 310 K	Time-resolved photoluminescence spectroscopy for minority carrier lifetime and surface recombination measurements.
Diffusion Time-of-Flight System	Cavity-dumped (40 kHz to 40 MHz) excitation, detection capability from 700 to 1,700 nm, 45 -ps time resolution	Minority-carrier diffusion, lifetime, and surface recombination measurements.
Superconductivity Test Station	65-300 K, 3.2-22.0 μA , 1-10 V rms	T_c measurement of superconducting materials.
Deep Level Transient Spectroscopy (DLTS)	DLTS spectra and transients from 77 to 320 K	Determination of trap ionization energies, emission rates, and capture cross-sections.

Capacitance-Voltage Measurement System

Capacitance as a function of voltage over the frequency range 100 Hz to 100 MHz

Determination of the effective doping concentration.

CELL AND MODULE PERFORMANCE GROUP

Instrument	Range/Capacity	Unique Features and Uses
Spectrolab X25 (With Multisource Attachment)	100 Wm ⁻² to 20,000 Wm ⁻² , user-controlled spectral and total irradiance 33 x 33 cm ² beam	Solar simulation under standard or user-defined reporting conditions.
Current vs Voltage (I-V) Measurement System	± 50 to ± 1 μV, ± 8 A to ± 1 pA, 0°C to 110°C, voltage bias rates from steady state to 200 V/sec	Efficiency measurements, secondary reference cell calibration, temperature coefficients, diode parameters, dark I-V, I-V measurement artifacts.
Spectral Response Measurement System	300-2,000 nm expandable to 10,000nm, light bias to ~5 suns, voltage bias to ± 40 V, current range 1 pA to 4 A, up to 100 cm diameter monochromatic beam	Quantum efficiency, device parameters. Capable of measuring modules or small cells.
Spectrolab Large Area Pulsed Solar Simulator (LAPSS)	2 x 2-m area at 1000 Wm ⁻² , ± 100 μA to ± 13 A full-scale current, ± 1 V to ± 70 V voltage range, custom data acquisition system	Module measurements, detect and correct I-V artifacts related to a pulsed light source's large bias rate.
Spectrolab Pulsed Concentrator Solar Simulator	10 x 20-cm area at 1 to 2000 suns, ±100 μA to ±13 A full-scale current, ±1 V to ±80 V voltage range, 1-msec pulse	Concentrator I-V measurements, correct bias rate, temperature, and spectral artifacts.
PV Calibration System	Two Newtonian trackers, four samples at a time biased to I _{sc} , temperature control and monitoring 40 samples at a time if I _{sc} and total irradiance measured separately and under global sunlight	Primary calibration of solar cells under direct or global sunlight; or modules under global light (fixed-tilt or normal incidence).
PV Rating Analysis System	I-V of 16 modules at 1-min intervals vs air temperature, sample temperature, wind speed, humidity, direct and diffuse irradiance, and spectra	Compare all of the various module rating methods at the same site and time interval with all relevant PV technologies.
LICOR Spectoradiometer	300-1,100 nm, 4-nm resolution, global light (integrating sphere), direct normal light (5.0° field of view), Teflon dome diffuser, fiber optic probe. Computer model extension of outdoor spectra to 300-4000 nm	Required for efficiency measurements and calibrations, simulator spectral characterization.

GER Spectroradiometer	300 to 1100 nm, 4-nm resolution global light (integrating sphere, diffusing plate), direct normal light (5.0° field of view)	Required for efficiency measurements and calibrations, simulator spectral characterization.
HP1000 Computer and Macintosh Computers		Control of measurement systems; data base management.
Standardized Outdoor I-V System	I-V of cells and modules, $\pm 10 \mu\text{A}$ to $\pm 40 \text{ A}$, $\pm 0.001 \text{ V}$ to $\pm 100 \text{ V}$ with air temperature, sample temperature, wind speed, humidity, direct and diffuse irradiance, spectra, and data base	Flexibility to evaluate any PV cell or module at one sun or under concentration. Designed to evaluate bias related artifacts.
Spire Solar Simulator	I-V measurements on modules and cells 0.1 mA to 20 A, 0-70 V	High throughput module measurements.

SURFACE INTERACTIONS, MODIFICATIONS AND STABILITY GROUP

Instrument	Range/Capacity	Unique Features and Uses
XPS/ISS/SIMS FAB SIMS/AES (Leybold LHS-10 System)	XPS: 2 to 10-mm area; ISS: 0.5 to 2-mm spot size; SIMS: 0.5 to 2-mm spot size; AES: 1- μm spot size. Detection sensitivities of 0.1 to 1 at. % for XPS, AES, and ISS; of ca. 10^{-4} at. % for SIMS	Depth profiling with a 1-mm $\leq$ 1-cm raster range. Thin-film deposition with QC monitor in a preparation chamber; translation of sample on heatable (to 800°C) - coolable (to -196°C) rods from preparation or high pressure chambers (to 10 atm) into the analysis chamber; four different surface analysis probes on one instrument; FAB source for FAB-SIMS.
Scanning Auger Microprobe (Physical Electronics 545C)	3.0- μm minimum size for electron beam; detection sensitivity of 0.1 to 1.0 at. % for Li to U	AES or SAM analysis while depth profiling; rapid-load lock and multiple sample carousel permits high throughput for routine analyses.
Quartz Crystal Microbalance System (Sycon-NREL)	Range of 10^6 ng/cm^2 ; detection sensitivity of 1 ng/cm^2 ; practical capacity for hydrophilic polymers is about 1.5 mg; for other solids, 100 mg; T from 15 to 75°C; P from vacuum to 1,500 torr	Measure adsorption/desorption of gases on solid overlayers adherent to a gold-coated quartz crystal; mass gain or loss during oxidation or reduction; permeation rates of gases through solids up to 100- μm thick; especially good for water vapor sorption studies.
Beam Microbalance (Sartorius 4300)	Capacity of 3 to 5 g; detection sensibility of 0.1 to 1 μg ; measuring range of 400 mg; T from -196° to 1,000°C. P from vacuum to 1,500 torr	Same applications as QCM. Samples (suspended by fibers) can be monitored for outgassing and desorption with an RGA.

Deposit Thickness Monitor (Inficon IC-6000)	Measure deposition rates 0.05 nm/min to over 10 nm/s and deposited thicknesses to 10,000 nm to less than 1% accuracy	Monitor vacuum-deposited overlayer thicknesses in the LHS-10 preparation chamber for preparing clean metal deposits and subsequent XPS/ISS/SIMS/ AES analysis without exposure to air.
Metallograph (LECO Neophot 21)	Mag: 80X to 2,000X polarization quantinet 800 image analysis	Optical microscopy with or without polarized light, Nomarski, prints/ slides, and image analysis.
Solar Furnace (NREL)	10-kW maximum flux, 250 W/cm, 40 mm FWHM	Long focal length in primary concentrators (7.05 m); capable of inserting secondary concentrator to boost flux to the range of 5000 W/cm ² ; fully automated operation and data acquisition.
Profilometers (Tencor Alpha-Step and Sloan Dektak)	Measurement range from 100-nm full scale to 100- μ m full scale	Measures step heights and surface topography with $\pm$ 1-nm sensitivity; auto-level, microscope X-Y translation stage for sample positioning 12.5- μ m and 5- μ m diameter tips available.
Oriel Model 6732 Solar Simulator	Unfiltered spectral output from 0.25 to 2.5 μ m at about 17 solar constants (collimated 5-cm ² output beam).	Equipped with filters and dichroic reflectors to limit spectral output to a desired range for photochemical studies.
Lambda-Physik EMG-50 Excimer Laser and FL-2000 Dye Laser	Monochromatic, coherent output, with wavelengths variable between 197-950 nm (1-cm ² output beam)	Complements the solar simulator in photochemical studies; excimer is currently set up for 308-nm output, and dye laser is now tuneable between 260 and 320 nm.
Polaron Series E6000 Vacuum Coater	10 ⁻⁷ torr vacuum capability, sputter or evaporative coating	Used to deposit thin films (usually of metals) onto smooth substrates; typical use is to prepare IR- reflective, metal-coated substrates for IR-external-reflection spectroscopy.

FTIR SPECTROSCOPIC RESEARCH AND SERVICE CENTER

Instrument	Range/Capacity	Unique Features and Uses
Nicolet System 800 High Resolution Mid-Infrared FTIR Spectrophotometer	Frequency range 7,800 to 500 cm ⁻¹ , resolution 0.1 cm ⁻¹ , sensitivity 10 ⁻⁵ O.D.	Collects high-resolution, low-noise, mid-infrared spectra of solid and liquid samples in transmittance, specular and diffuse reflectance, and attenuated total reflection modes; also used with FT-Raman accessory.
Nicolet FT-Raman Accessory	Frequency range 3,800-150 cm ⁻¹ Stokes	Collects Raman and photolumi- nescence spectra of solid and liquid samples.

Nicolet Nic-Plan FTIR Microscope	Minimum sample size 10 x 10 μm , translational resolution 1 μm , includes automated scanning stage and color micrography	Collects mid-infrared spectra of small-area solid samples in reflectance and transmittance modes; used with System 710.
Nicolet System 710 Medium-Resolution Mid-infrared FTIR Spectrophotometer	Frequency range 7,000 to 400 cm^{-1} (standard samples), 7,800-650 cm^{-1} (FTIR microscope), resolution 1.0 cm^{-1}	Primarily used with FTIR microscope, but has sample compartment for mid-infrared transmittance analysis.
Nicolet System 20F Medium Resolution Far-infrared FTIR Spectrophotometer	Frequency range 650 - 20 cm^{-1} , resolution 0.7 cm^{-1} , evacuable optics	Collects far-infrared spectra of solid samples in transmittance and diffuse reflectance modes.
Hansen High-TranCryostatic Sample Mount	Sample temperature control range 8.0 - 450 K	Provides temperature and illumination control for solid samples during infrared transmittance analysis <i>in vacuo</i> ; used with Systems 20F and 800.
Nicolet 7199b High-Resolution Mid-Infrared FTIR Spectrophotometer	Frequency range, 7800-500 cm^{-1} , expandable to 25,000-100 cm^{-1} , resolution 0.06 cm^{-1} , sensitivity 10^{-5} O.D.	Collects high resolution, low-noise, mid-infrared spectra of solid and liquid samples in transmittance, specular reflectance, and attenuated total reflection modes.

MATERIALS DURABILITY AND COMPONENT RELIABILITY RESEARCH

Instrument	Range/Capacity	Unique Features and Uses
Denver Instrument A200DS Electronic Analytical Balance	0.1-mg and 0.01-mg resolution	Accurate weights measurement.
DSET Suntest CPS System with a Black Panel Thermometer	1500 -W Xe burner, (20-cm x 28-cm) sample plate (removeable), and programmable timer	Tabletop exposure unit; easy operation for small and large samples.
Oriel Model 81281 UV-enhanced Solar Simulator with a Power Supply (Model 68820)	1000-W Xe lamp (reduced IR intensity)	For accelerated tests for UV degradation of polymer materials and mini-modules.
Oriel Photofeedback Controller (Model 68850)		Light intensity auto-feedback controller for solar simulator.
Oriel 100 W Xe Arc Lamp/Lamp Housing (Model 66021)	Can hold a 450 to 1000-W Xe or Xe(Hg) lamp	For photochemistry and other applications that require intense light.
Oriel Power Supply (Model 66820)	400 to 1000 W	Power supply for the 1000-W Xe lamp.
Oriel Ozone Eater (Model 66087)	Activated carbon fibers	Portable unit, useful for filtering ozone produced from 1000 -W Xe arc lamp.

Sunlighter RS/4 Test System (Model 15)	3 GE RS/4 UV lamps with a turntable	Test chamber for accelerated testing of materials.
HP-8452A UV-visible Spectrophotometer	190 nm to 820 nm, 2-nm resolution	Absorption and transmission measurements.
M.-M. Micromanipulator (Model 6000)	Optical microscope, XYZ-trans-portable platform with four needle probes	For microscopic examination and/or resistance measurement of small objects.
Lab-line Duo-Vac ovens (Three units), Two Mini-Vac Pumps	25°C to 260°C	General purpose heating or drying.
Orion pH Meter, Model 720A (With an Electrode Switch)	pH 0 to 14 and ion-selective analysis	pH measurement for aqueous solutions; useful for analysis of metal cations or anions.
Fluke 8050A Digital Multimeter	AC/DC, MA, V, Ohms	For current, voltage, and resistance measurement.
Keithley 485 Autoranging Picoammeter		Nano- to picoamper measurement.
Cole-Parmer 4658 and VWR Scientific 370 Stirrer/Hot Plate		Stirring and heating.
Omega Digital Thermometers (3)	Digital reading (0.1°C)	Temperature measurement.
Branson Model 3200 Ultrasonic Cleaner		Ultrasonic cleaning.
GraLab 900 Programmable Electronic Timer		Timer.

BIBLIOGRAPHY

1. Abou-Elfotouh, F.; Ahsour, S.; Alkuhaimi, S.; and Matson, R.; "The Formation and Junction Behavior of the Polycrystalline CdTe Interface with CdS and Metal Contact Thin Solid Films", (in press), 1993.
2. Abou-Elfotouh, F.; Ashour, S.; Alkuhaimi, S.A.; Zhang, J.; Dunlavy, D.J.; and Kazmerski, L.L.; "The Study of Defect Levels and Interface Properties of CdTe and CdS Polycrystalline Thin Films", Proc. Mat. Res. Soc. Symp., Vol. 238, pp. 335, 1992.
3. Abou-Elfotouh, F.A.; and Coutts, T.J.; "rf Planar Magnetron Sputtering of Polycrystalline CdTe Thin Film Solar Cells", International Journal on Solar Energy, Special Issue on CdTe Solar Cells, 1992.
4. Ahmad-Bitar, R.; Moutinho, H.; Ahrenkiel, R.; Abou-Elfotouh, F.; Dunlavy, D.; Keyes, B.; Matson, R.; Mason, A.; and Kazmerski, L.; "Study of the Process Treatments Used for High-Efficiency Thin-Film CdTe/CdS Solar Cells", Proc. 10th European Communities Photovoltaic Energy Conference, Montreaux, Switzerland, (Kluwer Academic Publishers, The Netherlands), 1992.
5. Ahrenkiel, R.K.; Keyes, B.M.; Dunlavy, D.J.; and Kazmerski, L.L.; "Improvement of Device Efficiency by Time-Resolved Photoluminescence Measurements", Proc. 10th European Communities Photovoltaic Energy Conference, Montreaux, Switzerland, (Kluwer Academic Publishers, The Netherlands), pp.533-536, 1992.
6. Ahrenkiel, R.K.; "Measurement of Minority-Carrier Lifetime by Time-Resolved Photoluminescence", Solid State Electronics, 35, pp. 239, 1992.
7. Ahrenkiel, R.K.; Keyes, B.M.; Lush, G.B.; Melloch, M.R.; Lundstrom, M.S.; and MacMillan, H.F.; "Minority-Carrier Lifetime and Photon Recycling in n-GaAs", J. Vac. Sci. Technol., A10, pp. 990, 1992.
8. Ahrenkiel, R.K.; Keyes, B.M.; Wang, L.; and Albright, S.P.; "Minority-Carrier Lifetime of Polycrystalline CdTe in CdS/CdTe Solar Cells", Proc. 22nd IEEE Photovoltaic Specialists Conference, pp. 940, 1991.
9. Ahrenkiel, R.K., Ed., "Properties of AlGaAs", INSPEC 1993, (Datareviews on minority-carrier lifetime, diffusivity), The Institution of Electrical Engineers, UK (in press), 1993.
10. Ahrenkiel, R.K., Editor, "Properties of InP", INSPEC 1991 (Datareviews on minority-carrier lifetime, diffusivity), The Institution of Electrical Engineers, UK, 1992.
11. Ahrenkiel, R.K., Guest Editor, Semiconductors and Semimetals, on Minority Carrier Properties of III-V Semiconductors, Academic Press, 1993.
12. Al-Jassim, M.M.; Jones, K.M.; Ahrenkiel, S.P.; Keyes, B.M.; Vernon, S.M.; and Karam, N.H.; "TEM and PL Characterization of GaAs and ZnSe/ZnCdSe Grown on Si", Proc. Solid State Devices and Materials Conf., Tsukuba, Japan, August 26-28, 1992.
13. Albin, D.; Carapella, J.; Gabor, A.; Tennant, A.; Tuttle, J.; Duda, A.; Matson, R.; Mason, A.; Contreras, M.; and Noufi, R.; "Fundamental Thermodynamics and Experiments in Fabricating High Efficiency CuInSe₂ Solar Cells by Selenization Without the Use of H₂Se", Proc. 11 PV AR&D Meeting, Golden, CO, May, 1992.
14. Arent, D.J.; Bertness, K.A.; Kurtz, S.R.; Bode, M.; and Olson, J.M.; "Optical Detection of Band Gap Variations Due to Ordering in Ga_{0.47}In_{0.53}As on InP", Proc. Mat. Res. Soc. Symp., 1992.
15. Asher, S.; Reedy, R.C.; Swartzlander, A.B.; Schuele, P.J.; and Huffman, M.; "SIMS Analysis of Trace Element Contamination in PZT", Proc. 39th National Symposium of the American Vacuum Society, J. Vac. Sci. Technol., Chicago, IL, Nov. 9-13, 1992.
16. Asher, S.E.; Secondary Ion Mass Spectrometry, "Microanalysis of Solids", Chapter 5, B.G. Yacobi, D.B. Holt, and L.L. Kazmerski, Eds., 1993.
17. Asher, S.E.; Kalejs, J.P.; Bathey, B.; "SIMS Analysis of Cr Gettering in Crystalline Silicon", Proc. 11th PV AR&D Meeting, Denver, CO, May 13-15, 1992.

18. Ashour, S.; Alkuhaimi, S.; Moutinho, H.; Matson, R.; and Abou-Elfotouh, F.; "Junction Formation and Characteristics of the CdS/CuInSe₂/Metal Interfaces", *Thin Solid Films* (in press), 1993.
19. Bode, M.; Ourmazd, A.; "Interfaces in GaAs/AlAs; Perfection and Applications", *J. Vac. Sci. Technol.*, **10**, 1992.
20. Bode, M.; Al-Jassim, M.M.; Tuttle, J.; and Albin, D.; "Microcharacterization of CuInSe₂ Grown by Coevaporation and Selenization", *Proc. Mat. Res. Soc. Symp.*, 1992.
21. Bode, M.; Al-Jassim, M.M.; Jones, K.M.; Matson, R.; "Microcharacterization of Polycrystalline Semiconductor Thin Films for Photovoltaic Applications", *Proc. 11th PV AR&D Meeting*, Denver, CO, May 13-15, 1992.
22. Chen, Z.; Matson, R.J.; and Burton, L.C.; "EBIC Study of Backside Hydrogen of Poly-Si Solar Cell Grain Boundaries", *Physica Status Solidi A - Applied Research*, V **132** (1), July 16, pp. 51-58, 1992.
23. Czanderna, A.W.; "Aspects of Surface Science for the Physical Chemistry Curriculum", NREL/TP-213-4500, December, 1991; for R. Moore and R. Schwenz, eds., *Physical Chemistry, Developing a Dynamic Curriculum*, ACS Books, Amer. Chem. Soc., Washington, DC, pp. 43-74, 1992.
24. Czanderna, A.W.; Landgrebe, A.R.; Eds., "Current Status, Research Needs, and Opportunities in Applications of Surface Processing to Transportation and Utilities Technologies", NREL/CP-412-5007 [also Critical Review in *Surface Chemistry*, Vol. 2, No. 1, CRC Press, Inc., Boca Raton, FL, 1993 (in press)], September, 1992.
25. Czanderna, A.W.; "Overview on Surface Processing — Status and Future Directions", *Proc. 14th Symposium on Applied Surface Analysis*, AVS, Ann Arbor, MI, June, 1992.
26. Dreszer, P.; Weber, E.R.; Khachatryan, A.; and Matson, R.J.; "Magnetic Susceptibility of Te Donors in Al_{0.3}Ga_{0.7}As", *Proc. ICPS-21*, Beijing, China, August, 1992.
27. Emery, K.; *Advances in Solar Energy Vol. 7*, "Efficiency Measurements of Photovoltaic Devices", Chapter 3, Karl Böer Ed., 1992.
28. Emery, K.A.; "Efficiency Measurements on Thin-Film PV Cells and Modules", *Proc. 11th Annual PV AR&D Meeting*, Golden, CO, May 13-15, 1992.
29. Emery, K.A.; "Measurement of Solar Cell Performance Parameters", *Proc. 6th International Photovoltaic Science and Engineering Conf.*, New Delhi, India, February 10-14, pp. 793-802, 1992.
30. Emery, K.A.; Beck, E.E.; Field, H.; and Rummel, S.; "PV Performance Measurements at NREL", *Proc. PV Performance and Reliability Workshop*, SERI/CP-411-5184 DE93000017, Golden, CO, Sept. 16-18, 1992.
31. Emery, K.A.; and Green, M.A.; *Progress in Photovoltaics Research and Applications Vol. 1*, "Solar Cell Efficiency Tables", pp. 25-29, 1993.
32. Freidman, D.J.; Kurtz, S.R.; Kibbler, A.E.; Bertness, K.A.; Kramer, C.; Matson, R.J.; Arent, D.J.; and Olsen, J.M.; "Anisotropic Electrical Transport and Surface Microstructure in GaInP₂", *Proc. Mat. Res. Soc. Symp.* Fall, 1992.
33. Gabor, A.M.; Hermann, A.M.; Tuttle, J.R.; Albin, D.S.; Swartzlander, A.B.; and Noufi, R.; "CuInSe₂ Thin Film Formation by Rapid Annealing of the Elemental Precursor", *Proc. 11th PV AR&D Meeting*, AIP Conference Proceedings, Denver, CO, May, 1992.
34. Jones, K.M.; Hasoon, F.S.; Swartzlander, A.B.; Al-Jassim, M.M.; Chu, T.L.; and Chu, S.S.; "The Morphology and Microstructure of Polycrystalline CdTe Thin Films for Solar Cell Applications", *Proc. EMSA*, pp. 1384, 1992.
35. Jung, D.R.; King, D.E.; and Czanderna, A.W.; "X-Ray Photoelectrospectroscopy of Organized Molecular Assembly-Copper Interfaces: The OH/Cu Interface", NREL/TP-412-5090 [also *Appl. Surf. Sci.*, in press. 1993], September, 1992.
36. Jung, D.R.; King, D.E.; and Czanderna, A.W.; "XPS of Organized Molecular Assembly/Copper Interfaces: HS(CH₂)₁₁CN/Cu", NREL/TP-412-5197, [also, *J. Vac. Sci. Technol.*, ²*Proc. 12th Intl. Vac. Cong. (IVC-12)*, ³*Proc. 8th Intl. Conf. on Solid Surf. (ICSS-8)*, ⁴*Appl. Surf. Sci.* (to be published)], October, 1992.

37. Kazmerski, L.L.; "Atomic-Level Imaging, Processing and Characterization of Defects and Surfaces Using Proximal Probe Techniques", Vacuum, 1992.
38. Kazmerski, L.L.; "Characterization of Photovoltaics: From Arrays to Atoms", Proc. 11th PV AR&D Meeting, Denver, CO, May 13-15, 1992.
39. Kazmerski, L.L.; and Emery, K.A.; "Photovoltaic Technologies: From Atoms to Arrays", Proc. World Renewable Energy Conference, Reading, UK, September, 1992.
40. Kazmerski, L.L.; and Emery, K.A.; "Photovoltaics: Research and Technology Development", Proc. Nordic Photovoltaic Electricity Meeting, Borlange, Norway, pp. 6-20, 1992.
41. Keyes, B.M.; "Minority-Carrier Lifetime of Compound Semiconductors in Polycrystalline CdTe", Proc. 11th PV AR&D Meeting, Denver, CO, May 13-15, 1992.
42. Keyes, B.M.; Emery, K.A.; and Ahrenkiel, R.K.; "Minority-Carrier Lifetime of Compound Semiconductors: Polycrystalline CdTe", R. Noufi, Ed., Proc. PV Advanced Research & Development Project, AIP Conference 268, Denver, CO, pp. 149-154, 1992.
43. King, D.E.; Czanderna, A.W.; and Spaulding, D.; "Charging Shifts During XPS Analysis of the Cu/Arachidic Acid Interface on Aluminum Oxide Films", J. Vac. Sci. Technol., A11(1), [also NREL TP-4120-4721], Jan/Feb, 1993.
44. King, D.E.; Czanderna, A.W.; and Spaulding, D.; "Interactions of Deposited Copper on COOH of 11-Mercaptoundecanoic Acid: An XPS Study", K. Mittal, Ed., Metallized Plastics, Plenum, NY, pp. 149-161, 1992.
45. Lovejoy, M.L.; Melloch, M.R.; Lundstrom, M.S.; Keyes, B.M.; Ahrenkiel, R.K.; de Lyon, T.J.; and Woodall, J.M.; "Comparative Study of Minority Electron Properties in p+-GaAs Doped with Beryllium and Carbon", Appl. Phys. Lett., 61, pp. 822, 1992.
46. Lovejoy, M.L.; Melloch, M.R.; Ahrenkiel, R.K.; and Lundstrom, M.S.; "Measurement Considerations for Zero-Field Time-of-Flight Studies of Minority-Carrier Diffusion in III-V Semiconductors", Solid State Electronics, 35, pp. 251, 1992.
47. Lundstrom, M.S.; Melloch, M.R.; Lush, G.B.; Patkar, M.P.; Young, M.; Durbin, S.M.; Gray, J.L.; MacMillan, J.F.; Keyes, B.M.; Levi, D.H.; and Ahrenkiel, R.K.; "Radiative Recombination and Photon Recycling in GaAs Solar Cells", Proc. 11th PV AR&D Meeting, AIP Proceedings, Golden, CO, 1992.
48. Lush, G.B.; MacMillan, H.F.; Keyes, B.M.; Lundstrom, M.S.; Ahrenkiel, R.K.; and Melloch, M.R.; "A Study of Minority-Carrier Lifetime versus Doping in n-Type GaAs by Metalorganic Vapor Deposition", J. Appl. Phys., 72(4), pp. 1436, 1992.
49. Lush, G.B.; Melloch, M.R.; Lundstrom, M.S.; MacMillan H.F.; Keyes, B.M.; Ahrenkiel, R.K.; "Measurement of Minority Carrier Lifetimes in n-Type GaAs and the Implications for Solar Cells", Proc. 22nd IEEE Photovoltaic Specialists Conference, pp. 182, 1991.
50. Lush, G.B.; Melloch, M.R.; Lundstrom, M.S.; Levi, D.H.; Ahrenkiel, R.K.; and MacMillan, H.F.; "Microsecond Lifetimes and Low Interface Recombination Velocities in Moderately Doped n-GaAs Thin Films", Appl. Phys. Lett., 61(20), 1992.
51. Lush, G.B.; Levi, D.H.; MacMillan, H.F.; Ahrenkiel, R.K.; Melloch, M.R.; and Lundstrom, M.S. "Microsecond Lifetimes in Moderately Doped n-GaAs Thin Films", Proc. Electronic Materials Conf., Cambridge, MA, 1992.
52. Lush, G.B.; MacMillan, H.F.; Keyes, B.M.; Ahrenkiel, R.K.; Melloch, M.R.; and Lundstrom, M.S.; "Photoluminescence Decay Study of Minority-Carrier Recombination in n-Type GaAs", Appl. Phys. Lett., (in press), 1992.
53. Margaritondo, G.; McKinley, J.T.; Rioux, D.; and Niles, D.W.; "Understanding and Controlling Semiconductor Interfaces: Spectroscopy and Spectromicroscopy", Appl. Surf. Sci., 56-58, pp. 713-722, 1992.
54. Matson, R.J.; "Recent Advances in Applications in Charge Collection Microscopy", Scanning Microscopy, Proc. 11th Pfefferkorn Conf. on the Physics of Generation and Detection of Signals Used for Microcharacterization, Univ. of Mass, August 10-14, 1992.

55. Menezes, S.; Noufi, R.; and Matson, R.J.; "New Configuration and Method for CuInSe_2 -Based Thin Film Solar Cells", Proc. 11th European Communities Photovoltaic Solar Energy Conference, Montreaux, Switzerland, October 10-12, 1992.
56. Moutinho, H.R.; Ahmad-Bitar, R.; Hasoon, F.S.; Ahrenkiel, R.K.; Dunlavy, D.J.; Keyes, B.M.; Mason, A.R.; Abou-Elfotouh, F.A.; Birkmire, R.W.; and Kazmerski, L.L.; "Study of the Process Treatments Used for High-Efficiency, Thin-Film CdTe Solar Cells", Proc. 10th European Communities Photovoltaic Solar Energy Conference, Montreux, Switzerland, 1992.
57. Nann, S.; and Emery, K.; "Spectral Effects on PV-Device Ratings", Solar Energy Materials, Vol. 27, pp. 189-216, 1992.
58. Naziripour, A.; Hermann, A.M.; Swartzlander, A.B.; Nelson, A.J.; and Dong, C.; "The Influence of Processing Conditions on the Morphology and Electronic Properties of Tl-Ba-Ca-Cu-O (TBCCO) Superconducting Thin Films", Proc. of the Beijing International Conference on High Tc Superconducting Thin Films (World Scientific, Pubs. Philadelphia, PA), 1993.
59. Nelson, A.J.; Frigo, S.; and Rosenberg, R.A.; "Photoemission Characterization of the H_2 Plasma Etched Surface of CdS ", J. Appl. Phys., 71(12), pp. 5881, 1992.
60. Nelson, A.J.; Niles, D.W.; Kazmerski, L.L.; Rioux, D.; Patel, R.; and Höchst, H.; "Photoemission Study on the Formation of Mo Contacts to CuInSe_2 ", J. Appl. Phys., 72(3), pp. 976, 1992.
61. Nelson, A.J.; Frigo, S.; and Rosenberg, R.A.; "Soft X-ray Photoemission Characterization of the H_2S Exposed Surface of p-InP ", J. Appl. Phys., 71(2), pp. 6086, 1992.
62. Nelson, A.J.; Niles, D.W.; Rioux, D.; Patel, R.; and Höchst, H.; "Soft X-ray Photoemission Investigation on the Effect of In Doping in CdS/CuInSe_2 Heterojunction Formation", J. Appl. Phys. 72(12), pp. 5888, 1992.
63. Nelson, A.J.; Niles, D.W.; Kazmerski, L.L.; Rioux, D.; Patel, R.; and Höchst, H.; "The Effect of In Doping in CdS/CuInSe_2 Heterojunction Formation: A Photoemission Investigation", Proc. 11th PV AR&D Meeting, AIP Conference Proceedings, No. 268, Denver, CO, pp. 228, 1992.
64. Nelson, A.J.; "The H_2S Plasma Exposed Surface of InP : A Photoemission Investigation", Proc. 39th National Symposium of the American Vacuum Society, Chicago, IL, Nov. 9-13, J. Vac. Sci. Technol., A11 (4), 1993.
65. Nelson, A.J.; Schwerdtfeger, C.R.; Wei, S-H; Zunger, A.; Rioux, D.; Patel, R.; and Höchst, H.; "Theoretical and Experimental Studies of the ZnSe/CuInSe_2 Heterojunction Band Offset", Appl. Phys. Lett. 61(12), 1993.
66. Niles, D.W.; Rioux, D.; and Höchst, H.; "A Photoemission Investigation of the SnO_2/CdS Interface: A Front Contact Interface Study of CdS/CdTe Solar Cells", J. Appl. Phys. 1993.
67. Niles, D.W.; "Band Offsets and Strain Relaxation in $\text{ZnTe/CdTe}(100)$ Heterostructures", Proc. 39th National Symposium of the American Vacuum Society, J. Vac. Sci. Technol., Chicago, IL, Nov. 9-13, 1992.
68. Niles, D.W.; Nelson, A.J.; Schwerdtfeger, C.R., Höchst, H.; and Rioux, D.; "Mo and Ni Schottky Barriers to CuInSe_2 (112)", Proc. Mat. Res. Soc. Symp., No. 260, Advanced Metallization and Processing for Semiconductor Devices and Circuits-II, pp. 299, 1992.
69. Niles, D.W.; Höchst, H.; and Rioux, D.; "Polarization Selection Rules in Photoemission from Valence Bands of Zinc Blende Semiconductors", Phys. Rev. B, pp. 12547, 1992.
70. Niles, D.W.; Höchst, H.; and Rioux, D.; "Valence Band Discontinuity at the ZnTe/CdTe Interface: Making Ohmic Contact to p-Type CdTe ", AIP Conference Proceedings 268, R. Noufi, Ed., pp. 279, 1992.
71. Niles, D.W.; and Höchst, H.; "Determination of the Bowing Parameter of the Split-Off Band in $\text{Cd}_{0.8}\text{Zn}_{0.2}\text{Te}$ (100) by Angle Resolved Photoemission Spectroscopy", Phys. Rev. B 46, pp. 1498, 1992.
72. Niles, D.W.; and Margaritondo, G.; "Electronic Properties of Semiconductor-Semiconductor Interfaces and Their Control Using Interface Chemistry", Atomic-Level Properties of Interface Materials, S. Yip and D. Wolf, Eds. (Chapman and Hall, London), pp. 592, 1992.

73. Niles, D.W.; and Höchst, H.; "Manifestation of Electric Dipole Selection Rules in Angle Resolved Photoemission Spectra from Zinc Bland Semiconductors", *J. Vac. Sci. Technol.*, **A10(4)**, pp. 1526, 1992.
74. Osterwald, C.R.; "Photovoltaic Standards Development Within ASTM", Proc. 11th PV AR&D Meeting, Denver, CO, May, 1992.
75. Osterwald, C.R.; and Dipppo, P.C.; Eds., "FY 1991 Measurements and Characterization Branch Annual Report", NREL/TP-412-5160, November, 1992.
76. Paranthaman, M.; Foldeaki, M.; Balzar, D.; Ledbetter, H.; Nelson, A.J.; and Hermann, A.M.; "Enhanced Flux Pinning via Chemical Substitution in Bulk Ti-2212", *Phys. Rev. B* (Submitted), 1992.
77. Pern, F.J.; "A Comparative Study of Solar Cell Performance Under Thermal and Photothermal Tests", Proc. PV Performance & Reliability Workshop, NREL/CP-411-5184, Golden, CO, pp. 327-344, 1992.
78. Pern, F.J.; "Luminescence and Absorption Characterization of Ethylene-Vinyl-Acetate Encapsulant for PV Modules Before and After Weathering Degradation", NREL/TP-213-4605 Revised, Polymer Degradation and Stability, August, 1992.
79. Pern, F.J.; and Czanderna, A.W.; "Characterization of Ethylene Vinyl Acetate (EVA) Encapsulant: Effects of Thermal Processing and Weathering Degradation of its Discoloration", *Solar Energy Materials and Solar Cells*, **25**, pp. 3-23, 1992.
80. Pern, F.J.; and Czanderna, A.W.; "Investigation of EVA Degradation Mechanisms", Proc. 11th PV AR&D Meeting, Denver, CO, May 13-15, 1992.
81. Pern, F.J.; and Czanderna, A.W.; "Spectroscopic Studies of Degradation of Ethylene Vinyl Acetate (EVA) Copolymer Encapsulant for PV Modules", Proc. 34th Rocky Mountain Conference on Analytical Chemistry, **No 186**, [also NREL/TP-412-4786], Denver, CO, July 28-August 3, 1992.
82. Pern, J.; and Czanderna, A.W.; "EVA Degradation Mechanisms Simulating Those in PV Modules", Proc. 11th PV AR&D, [also NREL/TP-412-4940], Denver, CO, May, 1992.
83. Perry, A.J.; Sartwell, B.D.; Valvoda, F.; Rafaja, D.; Williamson, D.L.; and Nelson, A.J.; "Residual Stress and the Effect of Implanted Argon in Films of Zirconium Nitride Made by Physical Vapor Deposition", *J. Vac. Sci. Technol.*, **A10(4)**, pp. 1446, 1992.
84. Pesaran, A.A.; Penney, T.R.; and Czanderna, A.W.; "Desiccant Cooling: State-of-the-Art Assessment", NREL/TP-254-4147, October, 1992.
85. Pitts, J.R.; Tracy, E.; and Shinton, Y.; "Applications of Solar Energy to Surface Modification Processes", Proc. DOE Sunraces Processing Workshop, NREL/CP-412-5007, A.R. Landgrebe and A.W. Czanderna, Eds., Boca Raton, FL, Dec. 10-12, 1992.
86. Pitts, J.R.; Tracy, E.; Shinton, E.; and Fields, C.L.; "Surface Modification Using Concentrated Solar Radiation", Proc. 1992 ASME/JSES/KSES Int. Solar Energy Conf., ASME New York, Maui, Hawaii, April 4-8, pp. 1107-1112, 1992.
87. Pugh, J.R.; Mao, D.; Zhang, J-G; Heben, M.J.; Nelson, A.J.; and Frank, A.J.; "A Metal:p-n-CdTe Schottky-Barrier Solar Cell; Photo-electrochemical Generation of a Shallow p-Type Region in n-CdTe", *J. Appl. Phys.*, **73** (in press), 1993.
88. Rocheleau, R.E.; Zhang, J.; Niles, D.W.; and Mason, A.; "Effect of Hydrogen Dilution on the Properties and Bonding in Plasma-Deposited Silicon Nitride", *J. Appl. Phys.*, July, 1992.
89. Rohde, S.L.; Nelson, A.J.; Mason, A.; and Sproul, W.D.; "Characterization of TiN Films Deposited Using Multi-Cathode Unbalanced Magnetrons", *J. Vac. Sci. Technol.*, **A10(4)**, pp. 1797, 1992.
90. Rosenwaks, Y.; Thacker, B.R.; Ahrenkiel, R.K.; and Nozik, A.J.; "Electron Transfer Dynamics at p-GaAs Liquid Interfaces", *J. Phys. Chem.* (in press), 1993.
91. Rosenwaks, Y.; Hanna, M.C.; Levi, D.H.; Szmyd, D.M.; Ahrenkiel, R.K.; and Nozik, A.J.; "Hot Carrier Cooling in GaAs: Quantum Wells vs Bulk", *Phys. Rev. B* **15**, 1993.

92. Sheldon, P.; Keyes, B.M.; Ahrenkiel, R.K.; and Asher S.E.; "Minority Carrier Lifetimes in MBE-Grown $\text{Al}_{1-x}\text{Ga}_x\text{As}/\text{GaAs}$ Double Heterostructures Doped With Aluminum", *J. Vac. Sci. Technol.* (in press), 1993.
93. Sopori, B.L.; Jones, K.M.; and Deng, X.J.; "Observations of Enhanced Hydrogen Diffusion in Solar Cell Si", *Appl. Phys. Lett.*, **61**, pp. 2560, 1992.
94. Tuttle, J.R.; Contreras, M.; Matson, R.J.; Bode, M.; Nelson, A.J.; Albin, D.S.; and Noufi, R.; "Growth Mechanisms, Characterization, and Device Performance of Thin-Film $\text{Cu}(\text{In,Ga})\text{Se}_2$ Fabricated by a Novel Two-Stage Process", *Proc. Mat. Res. Soc. Symp. Spring, II-VI Compound Semiconductor Photovoltaic Technology*, San Francisco, CA, 1993.
95. Tuttle, J.R.; Contreras, M.; Tennant, A.; Matson, R.; Duda, A.; Carapella, J.; Albin, D.; and Noufi, R.; "Novel Processing and Device Structures in Thin-Film CuInSe_2 -Based Solar Cells", *Proc. 11th PV AR&D Meeting, AIP Proceedings*, Denver, CO, May 13-15, 1992.
96. Tycko, R.; Dabbagh, G.; Kurtz, S.R.; and Goral, J.P.; "Quantitative Study of Atomic Ordering in GaInP by ^{31}P Nuclear Magnetic Resonance", *Phys. Rev. B* **45**, pp. 13452, 1992.
97. Uchida, H.; Curtis, C.J.; Prashant, P.V.; Kamat, V.; Jones, K.M.; and Nozik, A.J.; "Optical Properties of GaAs Nanocrystals", *J. Phys. Chem.*, **96**, pp. 1156, 1992.
98. Venkatasubramanian, R.; Posthill, J.B.; Timmons, M.L.; Ehsani, H.; Ghandhi, S.K.; Keyes, B.M.; and Ahrenkiel, R.K.; "Aspects of High Minority-Carrier Lifetime GaAs on Si Using a Novel SiGe/Ge Buffer", *Appl. Phys. Lett.*, **60**, pp. 886, 1992.
99. Webb, J.D.; and Johnson, E.J.; "FTIR Analysis of Contaminated Bondlines", *Proc. Joint Army-Navy-Air Force Non-Destructive Analysis Subcommittee (ANNAF/ NDES)*, Seattle, Washington, July, 1992.
100. Zhang, J.; Sheldon, P.; and Ahrenkiel, R.K.; "A GaAs Hall Probe for Characterizing High Temperature Superconductors", *J. Appl. Phys.*, **63**, pp. 2259, 1992.
101. Zhu, J.G.; Al-Jassim, M.M.; Karam, N.H.; and Jones, K.M.; "Defect Reduction in GaAs Grown on Si by Using Saw-Tooth-Patterned Substrates", *Proc. Mat. Res. Soc., Fall Meeting*, Boston, Mass, November, 1992.

STAFF BIOGRAPHIES

Fouad Abou-Elfotouh (NREL 1986): Senior Scientist. Research and support interests and responsibilities: electro-optical properties (including defect states and their behavior) of semiconductor (thin films and single crystals); fabrication, characterization, and modeling of heterojunction devices, solar cell back contacts; and development of spectroscopic ellipsometer.

Richard K. Ahrenkiel (NREL 1981): Principal Scientist and Group Leader. Research and support interests and responsibilities: materials characterization by photoluminescence and diffusion measurements; deep-level-transient-spectroscopy; C-V measurements; and superconductor characterization.

Mowafak M. Al-Jassim (NREL 1983): Senior Scientist and Group Leader, Materials Science. Research and support interests and responsibilities: transmission electron microscopy (TEM); scanning electron microscopy (SEM); defect analysis in semiconductors, and epitaxial growth by MOCVD and MBE.

Sarah (Sally) Asher (NREL 1985): Senior Scientist, Analytical Chemistry. Research and support interests and responsibilities: surface science; operation and maintenance of SIMS facility.

Elvira Beck (NREL 1987): Master Technician. Research and support interests and responsibilities: PV cell measurements and characterization by area, spectral response; and quantum efficiency; intensity, current vs. voltage, and reference cell calibrations.

Michael H. Bode (NREL 1992): Senior Scientist. Research interests and responsibilities: transmission electron microscopy (TEM); scanning electron microscopy (SEM); structural, electrical and optical characterization of semiconductors; semiconductor interface analysis.

Alvin W. Czanderna (NREL 1978): Research Fellow and Group Leader. Research and support interests and responsibilities: surface science; reactions at interfaces; stability and durability of multilayer thin-film devices; interactions at polymer/metal (oxide) interfaces; surface analysis; ultramicrogravimetry.

Patricia C. Diplo (NREL 1980): Administrative Assistant. Research and support interests and responsibilities: supports five of the groups within the branch and prepares branch correspondence; reports; etc.; organizes day-to-day branch operations.

Donald J. Dunlavy (NREL 1981): Staff Scientist. Research and support interests and responsibilities: minority carrier characterization by photoluminescence and diffusion measurements; design, modification; and maintenance of all test equipment.

Keith A. Emery (NREL 1980): Senior Scientist and Group Leader. Research and support interests and responsibilities: PV performance characterization by current versus voltage, temperature; spectrum, and intensity; PV calibration; quantum efficiency; PV standards.

Halden Field (NREL 1992): Associate Scientist. Research and support interests and responsibilities: solar cell performance and characterization equipment, software, and methods, including current vs. voltage, spectral response, and calibrations.

Clark L. Fields (NREL 1990) Visiting Professional (Summer), Prof. of Chemistry at the University of Northern Colorado, Greeley. Research and support interests and responsibilities: rapid thermal processing of materials; metal/organic chemistry; boron chemistry; chemical vapor deposition; ceramic superconductors.

Amy B. Swartzlander-Franz (NREL 1980): Associate Scientist. Research and support interests and responsibilities: characterization of solar and electronic devices, including superconductors, using SAM; AES, and XPS.

Falah Hasoon (NREL 1990): Visiting Professional. Research and support interests and responsibilities: scanning electron microscopy; luminescent properties, and defect examination in semiconductors.

Greg Herdt (NREL 1991): Research Associate. Research and support interest and responsibilities: applied surface science; sorption phenomena of desiccant materials using microgravimetric and flow techniques; computerized evaluation and modeling of sorption processes.

Kim M. Jones (NREL 1981): Staff Scientist. Research and support interests and responsibilities: transmission electron microscopy; analytical electron microscopy; defect analysis in semiconductors.

David Jung (NREL: 1992): Postdoctoral Research Associate, Research and support interests and responsibilities: Metal/organic interface interactions of deposited metals on organized molecular assemblies using XPS, contact angle, and STM.

Elizabeth (Jo) Johnson (NREL 1990): AWU Student Fellow. Research and support interests and responsibilities: Fourier transform infrared (FTIR) spectroscopy and analysis.

Lawrence L. Kazmerski (NREL 1977): Principal Scientist and Branch Manager. Research and support interests and responsibilities: scanning tunneling microscopy; surface and interface analysis research.

Brian M. Keyes (NREL 1988): Associate Engineer. Research and support interests and responsibilities: minority-carrier characterization by photoluminescence and diffusion measurements; modeling of the above measurements; computer analysis and interfacing.

David King (NREL 1989): Staff Analytical Chemist. Research and support interests and responsibilities: surface analysis; FTIR spectroscopy; thin films and interfaces.

Dean Levi (NREL 1990): Research Associate. Research and support interests and responsibilities: time-resolved photoluminescence measurements of minority carrier lifetime; photon recycling; surface recombination velocity; chemical passivation of surface defects. Also extending laboratory capabilities through development of new measurement techniques.

Alice Mason (NREL 1984): Master Technician. Research and support interests and responsibilities: sample preparation for microscopy examination.

Richard Matson (NREL 1979): Staff Scientist. Research and support interests and responsibilities: scanning electron microscopy; X-ray microanalysis; defect examination in semiconductors and luminescent properties.

Helio Moutinho (NREL 1991): Research Associate. Research and support interests and responsibilities: materials characterization by scanning tunneling microscopy.

Art J. Nelson (NREL 1985): Senior Scientist and Group Leader. Research and support interests and responsibilities: surface and interface analysis research; surface and grain boundary phenomena in semiconducting and superconducting materials; synchrotron radiation photoemission on crystalline, polycrystalline, and amorphous materials; growth and characterization of II-VI semiconductors; plasma modification of surfaces.

David W. Niles (NREL 1991): Staff Scientist. Research and support interests and responsibilities: characterization of PV materials; devices and modules; surface and interface phenomena; measurement-system development.

Carl Osterwald (NREL 1982): Staff Scientist. Research and support interests and responsibilities: measurement system design and development; primary PV reference cell calibration; spectral response; current versus voltage measurements.

F.J. Pern (NREL 1984): Senior Scientist. Research and support interests and responsibilities: material fabrication and characterization; spectral, analytical, and electrochemical characterization of PV encapsulant polymers, metalization, and other module materials; module performance testing and analysis of failure mechanisms.

J. Roland Pitts (NREL 1979) Senior Physicist. Research and support interest and responsibilities: surface modification using particle beams; surface and interface science; stimulated desorption; transient thermal processes; optical and physical properties of thin films.

Robert Reedy (NREL 1992): Staff Scientist. Research and support interests and responsibilities: Materials characterization by secondary ion mass spectrometry; surface and interface analysis, trace element analysis, equipment maintenance and repair.

John D. Webb (NREL 1978): Senior Chemist and Center Manager. Research and support interests and responsibilities: Fourier Transform Infrared (FTIR) spectroscopy; polymer chemistry; photochemistry; and operation, maintenance, and business development for the FTIR Spectroscopic Research and Service Center.

Regina Witherspoon (NREL, 1990): Administrative Assistant. Research and support interests and responsibilities: supports Materials Durability and Component Reliability Group and the Surface Interactions Modifications, and Stability Group by the preparation of correspondence, reports, etc.; day-to-day group operations.

Jue Zhang (NREL, 1990): Research Associate. Research and support interests and responsibilities: deep-level-transient spectroscopy.

Jane Zhu (NREL, 1991): Research Associate. Research and support interests and responsibilities: materials science: transmission electron microscopy; structure and properties of materials, defects, and interfaces in heterostructures.

COOPERATIVE LABORATORIES

Advanced Photovoltaic Systems
Ain Shams University, Egypt
Airtech Corporation
Alpha Solarco
Alabama Power Company
Argonne National Laboratory
Arizona State University
Armco Research and Technology
Applied Solar Energy Corporation
AstroPower, Inc.
AT&T Bell Laboratories
Ben Gurion University, Israel
BHEL, India
Boeing Aerospace Company
Brooklyn Polytechnic Institute
Brookhaven National Laboratories
Brown University
California Institute of Technology
Cargocaire Engineering, Inc.
Carnegie-Mellon University
Chronar Corporation
Colorado School of Mines
Colorado State University
Coors Ceramic
Cornell University
Crystal Systems, Inc.
Duke University
Eaton Corporation
EIC Laboratories
Electrotechnical Laboratory, Japan
ENEA, Italy
Energy Conversion Devices
ENTECH, Inc.
Electric Power Research Institute
EXXON Research
Florida Solar Energy Center
Ford Aerospace
Franhofer Institute for Solar Energy Germany
Fuji Electric, Japan
Georgia Institute of Technology
Georgia Tech Research Institute
Glasstech Solar
Golden Photon
Grumman Aerospace Corporation
GTE Laboratories
Harvard University
Howard University
Hughes Research Laboratories
IBM
Indian Institute of Technology, Delhi

Institute of Energy Conversion
Institute for Non-Ferrous Metals, Beijing, China
Instituto Militar de Engenharia, Brazil
International Energy Foundation
International Solar Electric Technologies
Iowa State University
Jet Propulsion Laboratory
King Abdul-Aziz University, Saudi Arabia
Kyocera
Kopin Corporation
Lawrence Berkeley Laboratories
Louisiana State University
Mankato State University
Man-Tech Development, Inc.
Martin Marietta
Massachusetts Institute of Technology
Materials Research Group
Matsushita, Japan
MIT Lincoln Laboratory
Mobil Solar Energy Corporation
Montana State University
Motorola
NASA Lewis Research Center
National Institute for Silicon Technology, Pakistan
National Physical Laboratory, New Delhi, India
National Institute for Standards and Technology
Naval Research Laboratories
NESTE, France
Newcastle-Upon-Tyne Polytechnic, England
Nippon Telegraph & Telephone, Japan
North Carolina State University
Oak Ridge National Laboratory
Oregon State University
Osaka University, Japan
Pacific Gas and Electric
Pennsylvania State University
Photocomm
Photon Energy, Inc.
Princeton University
PTB, Braunschweig, Germany
Purdue University
Reed College
Rensselaer Polytechnic Institute
Research Triangle Institute
Sandia National Laboratories
Santa Barbara Research Center
Sanyo, Japan
Science Applications International Corporation
Shanghai Institute of Metallurgy, China
Siemens Solar Industries
State University of New York
Solar Cells, Inc.
Solarex Corporation
Solec International, Inc.
Solens, France

Spectrolab
Spire Corporation
Stanford University
Syracuse University
Texas Instruments, Inc.
Tideland Signal, Inc.
University of Colorado
University of Delaware
University of Florida
University of Illinois
University of New South Wales
University of North Carolina
University of Oregon
University of Sao Paulo, Brazil
University of Southern California
University of South Florida
University of Texas
University of Toledo
University of Utah
University of Washington
University of Wisconsin
United Solar Systems Corporation
Utility Power Group
Varian Associates
Washington State University
Weizmann Institute of Science, Israel
Westinghouse Electric Corporation
Wind Boron
Wuhan University, China
Xerox PARC

Document Control Page	1. NREL Report No. NREL/TP-412-5422	2. NTIS Accession No. DE93000094	3. Recipient's Accession No.
4. Title and Subtitle FY 1992 Measurements and Characterization Branch Annual Report			5. Publication Date March 1993
			6.
7. Author(s) P.C. Dippo, Editor			8. Performing Organization Rept. No.
9. Performing Organization Name and Address National Renewable Energy Laboratory 1617 Cole Blvd. Golden, CO 80401			10. Project/Task/Work Unit No. PV312001
			11. Contract (C) or Grant (G) No. (C) (G)
12. Sponsoring Organization Name and Address National Renewable Energy Laboratory 1617 Cole Blvd. Golden, CO 80401-3393			13. Type of Report & Period Covered Technical Report 1 February 1992-31 January 1993
			14.
15. Supplementary Notes NREL technical monitor: None.			
16. Abstract (Limit: 200 words) This report describes work done by the Measurements and Characterization Branch of the National Renewable Energy Laboratory (NREL) during FY 1992 to provide comprehensive photovoltaic (PV) materials, devices, characterization, measurement, fabrication, modeling research, and support for the international PV research community, in the context of the U.S. Department of Energy's Photovoltaic Research Program goals. This report summarizes the progress of the branch from 1 February 1992 through 31 January 1993. The eight technical sections present a succinct overview of the capabilities and accomplishments of each group in the branch. The branch is comprised of the following groups: Surface and Interface Analysis; Materials Characterization; Device Development; Electro-optical Characterization; Advanced PV Module Performance and Reliability Research; Cell Performance Characterization; Surface Interactions, Modification, and Stability; and FTIR Spectroscopic Research.			
17. Document Analysis a. Descriptors measurements ; characterization ; devices ; materials ; fabrication ; modeling ; photovoltaics ; solar cells b. Identifiers/Open-Ended Terms c. UC Categories 270			
18. Availability Statement National Technical Information Service U.S. Department of Commerce 5285 Port Royal Road Springfield, VA 22161			19. No. of Pages 31
			20. Price A03