AIM

Association for Information and Image Management

1100 Wayne Avenue, Suite 1100
Silver Spring, Maryland 20910
301/587-8202

Centimeter

Inches

MANUFACTURED TO AIM STANDARDS
BY APPLIED IMAGE, INC.

DECLASSIFIED

HW-69941
Page 1

COEXTRUSION PROCESS SPECIFICATIONS

ENGINEERING OPERATION
FUELS PREPARATION DEPARTMENT

August 1961

RESERVED DATA
This Document contains Restricted Data as defined by the Atomic Energy Act of 1954. Its transmission or the disclosure of its contents in any manner to any unauthorized person is prohibited.

HANFORD ATOMIC PRODUCTS OPERATION
RICHLAND, WASHINGTON

FEB 03 1962

NOTICE

This report was prepared for use within General Electric Company in the course of work under Atomic Energy Commission Contract AT(45-1)-1350, and any views or opinions expressed in the report are those of the authors only. This report is subject to revision upon collection of additional data.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A: Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B: Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

MASTER

**SPECIAL RE-REVIEW
FINAL DETERMINATION
DECLASSIFICATION CONFIRMED**

BY JW Jordan DATE 9-1-81
BY PDorwin DATE 9-21-81

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

CLASSIFICATION CANCELLED

Per Doc, May 1973

By B. Jones 2-7-74

DECLASSIFIED

COPY 24 OF 50

THIS PAGE IS UNCLASSIFIED

DISTRIBUTION

OFFSITE

1. P. Loewenstein,
Nuclear Metals, Inc., Concord, Mass.
- 2-3. P. M. Midkiff,
U.S. Atomic Energy Commission
Hanford Operations Office

ONSITE

4. F. W. Albaugh
5. W. K. Alexander
6. T. W. Ambrose
7. R. I. Beaver
8. H. E. Berg
9. A. G. Blasewitz
10. J. H. Brown
11. J. J. Cadwell
12. A. C. Callen
13. D. L. Cornell
14. T. B. Correy
15. R. L. Dickeman
16. R. L. Dillon
17. K. Drumheller
18. T. W. Evans
19. S. M. Gill
20. O. H. Greager
21. T. R. Groupman
22. A. E. Guay
23. J. L. Guthrie
24. W. G. Hudson
25. W. R. Kirk
26. W. K. Kratzer
27. L. E. Kusler
28. G. A. Last
29. L. H. McEwen
30. J. E. Minor
31. W. N. Mobley
32. T. D. Naylor
33. I. V. Nelson
34. J. W. Nickolaus
35. K. W. Norwood
36. P. G. Rhoades
37. G. W. Riedeman
38. J. E. Ruffin
39. C. H. Shaw
40. W. E. Stavig
41. J. T. Stringer
- 42-43. R. E. Tomlinson
44. F. W. Woodfield
45. D. C. Worlton
46. H. F. Zuhr
47. Record Copy
48. 300 Area Files
- 49-50. Extra

TABLE OF CONTENTS

- I. Approval Sheet
- II. Scope and Intent of Specifications
- III. Coextrusion Process Flow Sheet
- IV. Specifications

CX-100.0 COMPONENTS, MATERIALS AND TOOLING

	<u>No of</u> <u>Pages</u>
101.0 Uranium Billet Material	2
102.0 Uranium Billet Fabrication	3
110.0 Zircaloy Cladding Shells	3
120.0 Zircaloy End Caps	2
130.0 Zirconium-Beryllium Braze Alloy	2
140.0 Zircaloy-2 Supports and Locking Devices	2
160.0 Steel Support Shoe	1
170.0 Copper Extrusion Materials	3
180.0 Tool Designs and Preparation	1
190.0 Extrusion Cut-offs	1

CX-200.0 COMPONENT AND MATERIAL PREPARATION

201.0 Uranium Billet Cleaning and Inspection	1
210.0 Zircaloy Cladding Component Cleaning and Inspection	1
220.0 Zircaloy End Cap Cleaning and Inspection	1
230.0 Braze Alloy Cleaning and Inspection	1
240.0 Zircaloy Support and Locking Device Cleaning and Inspection	1
250.0 Steel Support Shoe Cleaning and Inspection	1
270.0 Copper Components-Cleaning and Inspection	1

CX-300.0 BILLET ASSEMBLY

301.0 Billet Assembly	2
-----------------------	---

CX-400.0 EXTRUSION

401.0 Billet Pre-extrusion Lubrication	1
410.0 Billet Preheat	1
420.0 Tool Cleaning, Preheat and Lubrication	1
430.0 Cut-off Preparation and Preheat	1
450.0 Extrusion Operation	1

CX-500.0 FINISHING OPERATION

501.0 Extruded Tube Sectioning	1
505.0 Copper Removal and Zircaloy Etching	1
515.0 End Closure Recessing	1
520.0 Pre-Braze Cleaning	1
525.0 End Closure Brazing	2
530.0 Beta Heat Treatment	1
535.0 Straightening	1
540.0 End Machining	1

TABLE OF CONTENTS (Continued)

		<u>No. of Pages</u>
545.0	Abrasive Cleaning	1
550.0	Preweld Bright Etch	1
555.0	End Closure Welding	1
560.0	Fuel Element Identification	1
565.0	Support and Locking Device Welding	1
570.0	Final Bright Etch	1
575.0	Autoclave Testing	2
585.0	Final Inspection and Assembly	1
590.0	Storage and Shipment	1
CK-600.0	<u>PRODUCT EVALUATION AND TESTING</u>	
615.0	Extrusion Sample Evaluation	2
620.0	Clad-Core Bond Test	1
625.0	Clad Thickness Test	1
635.0	Cap-Core Bond Test	1
640.0	Cap-Clad Bond Test	1
655.0	Autoradiographic Clad Thickness Test	1
660.0	Reference Table of Critical Dimensions	2

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

COEXTRUSION PROCESS SPECIFICATIONS

ENGINEERING OPERATION
FUELS PREPARATION DEPARTMENT

AUGUST 1961

ISSUED BY: S. M. Gill 8/22/61
S. M. Gill, Manager,
Coextruded Product Engineering-FPD Date

APPROVED BY: L. H. McEwen 8/24/61
L. H. McEwen, Manager,
Engineering Operation-FPD Date

ACCEPTED BY: W. N. Mobley 8/22/61
W. N. Mobley, Manager
Manufacturing Operation-FPD Date

ENDORSED BY: O. H. Greager 8/23/61
O. H. Greager, Manager,
Research & Engineering Operation-IPD Date

DECLASSIFIED

HW-69941

Page 6

SCOPE AND INTENT OF SPECIFICATIONS

These Specifications have been prepared for the M-reactor fuel as required by Organization and Policy Guide No. 44.2. It is intended that these specifications provide the framework on which the overall control and guidance of the manufacturing process shall be built. It is realized that in the instant case, where a completely new process is being put into operation, many changes will become necessary in the process, and likewise in the specifications, before appreciable quantities of material have been produced. It is planned that a procedure will be established for use during the first few months of operation whereby minor changes in these specifications can be made and approved by the Manager, Coextruded Product Engineering, with endorsement by the Supervisor, Reactor Fuels, IPD, and acceptance by the Manager, Coextrusion Shop and the Manager of Quality Control. Such procedure will be used until the first general revision of the specifications which can be expected not later than January 1, 1962.

These specifications have been prepared with the intent to detail those things required to assure that the process will produce the desired product. To further assure the utmost in quality of the fuel, it is intended that the FPD Engineering staff exercise prior review and endorsement of the Quality Control Standards to make sure they are in conformance with the intent of these specifications and that they reflect the best known technology.

The above requirements notwithstanding, it will still be necessary that all parties concerned with the fabrication of a satisfactory fuel load for the NPR, work closely to insure that misunderstandings are minimized; that improvements are incorporated as soon as practical; and that the best possible fuel is produced.

These specifications do not cover certain situations which may arise relating to reworking of material which has been rejected for one cause or another. It is to be understood that any material which can be reworked and still meet all the requirements of these specifications shall be accepted. Disposition of material which can not so qualify shall be the subject of supplemental specifications.

DECLASSIFIED

COEXTRUSION PROCESS FLOW SHEET

III COPPER COMPONENTS

1. Receiving Inspection
2. Cleaning
3. Cleaning Inspection
4. Cap Assembly & Welding
5. Cap Assembly Test
6. Can Assembly & Welding
7. Can Assembly Test

I URANIUM BILLETS

1. Receiving Inspection
2. Billet Pickle
3. Billet Pickle Inspection

II ZIRCALOY-2 COMPONENTS

Billet Clads

1. Receiving Inspection
2. Cleaning
3. Cleaning Inspection

IV BILLET ASSEMBLY

1. Billet Component Assembly
2. Billet Welding
3. Evacuation & Leak Test
4. Evacuation Tube Cutoff

VII STEEL SUPPORT SHOES

1. Receiving Inspection
2. Cleaning
3. Cleaning Inspection

V EXTRUSION

1. Billet Lubrication
2. Billet Preheat
3. Tool Preparation
4. Extrusion
5. Extruded Tube Handling

VI FUEL TUBE PREPARATION

1. Cut to Length
2. Destructive Test Evaluation
3. Copper Removal
4. Zircaloy Stripping
5. Surface, Dimension, N.D. Audit and Temporary Marking
6. End Closure Recessing
7. Pre-Braze Cleaning
8. End Closure Brazing
9. Beta Heat Treat
10. Heat Treat Inspection
11. Straightening
12. End Closure Machining
13. Abrasive Cleaning
14. End Closure Cleaning
15. End Closure Welding
16. Nondestructive Test
17. Degrease
18. Support Welding
19. Support Weld Inspection
20. Final Etch
21. Assembly & Autoclave
22. Disassembly & Autoclave Inspection
23. Outer Tube Steel Support Assembly
24. Final Assembly
25. Final Inspection & Storage

(II) END CAPS

4. Receiving Inspection
5. Cleaning
6. Cleaning Inspection

(II) BRAZE PIECES

7. Receiving Inspection
8. Cleaning
9. Cleaning Inspection

(II) SUPPORTS-ZIRCALOY

10. Receiving Inspection
11. Cleaning
12. Cleaning Inspection

UNCLASSIFIED

UNCLASSIFIED

HW-69941
Page 7

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 2	COPY NO.
	DATE August 9, 1961	
	SPECIFICATION NO. CX-101.0	
SPECIFICATION TITLE: URANIUM BILLET MATERIAL		

101.1 Basis

To insure that the uranium core of a coextruded fuel will sustain reactor operations, the coextrusion billet shall meet the following specifications for quality, physical properties and composition.

101.2 Material Specifications

101.2.1 Chemical Composition

Uranium metal provided for N-reactor fuel shall be of the following composition:

Beryllium	-	10	ppm, Maximum	
Boron	-	0.25	"	"
Cadmium	-	0.2	"	"
Carbon	-	500	"	"
Chromium	-	25	"	"
Copper	-	75	"	"
Hydrogen	-	2.0	"	"
Iron	-	200	"	" , 100 ppm, Minimum
Magnesium	-	25	"	"
Manganese	-	25	"	"
Nickel	-	100	"	"
Nitrogen	-	75	"	"
Silicon	-	140	"	" , 75 ppm, Minimum
Zirconium	-	100	"	"
Uranium	-	Remainder, except for other routinely occurring impurities which are not specified for analysis.		

101.2.2 Isotopic Composition

Uranium metal produced under this specification shall contain 0.947 ± 0.006 per cent U-235, except for that material required for poison loading which shall be natural.

101.2.3 Density

Minimum density for material produced under this specification shall be 18.90 grams per cubic centimeter.

101.2.4 Metal Quality

The final fabricated surfaces of each billet shall be free of metal quality defects, such as, but not limited to, seams, cracks and abnormal striations.

However, to meet this specification, not more than three longitudinal defects may be removed from the OD and ID each, providing these defects

<div style="text-align: center;"> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS </div>	DOCUMENT NO. HW-59941	
	PAGE NO. 2 of 2	COPY NO.
	DATE August 9, 1961	
SPECIFICATION TITLE: URANIUM BILLET MATERIAL (continued)	SPECIFICATION NO. CK-101.0 (cont.)	

are not over two inches long or more than 0.015 inches deep. Such defects shall be removed in such a way as to preserve the general curvature of the surfaces. Billets shall not be rejected for defects on the end surfaces provided such defects are contained entirely in metal which will be cropped as "end defect".

101.2.5 Dimensions*

All uranium billets produced under this specification shall be machined to meet the requirements of Drawing H-3-17076, Sheet 2, Revision 0, or H-3-17077, Sheet 2, Revision C.

*Note: The dimensional tolerance requirements of this specification (101.2.5) were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided satisfactory billet assembly can be carried out and there is no significant effect on the coextruded fuel section dimensional characteristics. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

DECLASSIFIED

DECLASSIFIED

[REDACTED]	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 3	COPY NO.
HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS		DATE August 9, 1961
SPECIFICATION TITLE: URANIUM BILLET FABRICATION		SPECIFICATION NO. CX-102.0

102.1 Basis

Uranium billets capable of being fabricated into dimensionally acceptable co-extruded fuel tubes must be fabricated under close control to insure a uniform product and by a specific sequence of operations to produce a correct metallurgical structure.

102.2 Process Specifications

102.2.1 Casting

a) Furnace Charge

The crucible charge shall consist of 15% maximum cleaned and pickled briquettes and a minimum of two derbies weighing together not less than 50% total charge weight. The remaining charge shall consist of cleaned and pickled, recastable solid scrap, excluding "drip crops".

b) Casting Practice

All melting and casting operations shall be done under sufficient vacuum to prevent atmospheric contamination and to degas the melt. Heating shall be by induction to promote thorough homogenization of the melt.

The heating and casting cycle shall incorporate the best technology and practice available to insure high quality, high purity castings.

c) Mold and Crucible Coatings

All parts of the crucible exposed to the melting charge shall be coated before each use with a wash of $MgZrO_3$.

All interior surfaces of the mold shall be flame sprayed before each use with $MgZrO_3$.

d) Cast Ingot Size

The ingot may be cast either solid or hollow. The overall dimensions shall be as follows:

O.D.	-	11 + 1/4 inches
		11 - 1/8 "
Length	-	20 to 33 "

e) Cropping

Two crops shall be made. The first, or "drip crop", shall remove a minimum of two (2) inches of metal from the center of the

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 2 of 3	COPY NO.
SPECIFICATION TITLE: URANIUM BILLET FABRICATION (continued)	DATE August 9, 1961	
	SPECIFICATION NO. CX-102.0 (cont.)	

of the casting top. The second, or "top crop", shall remove at least one (1) inch of metal immediately below the drip crop.

102.2.2 Heat Treatment

a) Media

Heating shall be done in either Liquid Heat 980 or NuSal. Quench shall be tap water.

b) Cycle

All cropped ingots shall be heat treated according to the following cycle:

Salt Temperature	-	1350 $\pm$ 20°F
Time in Bath	-	60 $\pm$ 2 minutes
Transfer Time to Quench	-	19 $\pm$ 1 second
Quench Water Temperature	-	85 $\pm$ 15°F

102.2.3 Drilling

If ingots are cast solid, they shall be drilled to an appropriate ID after heat treatment.

102.2.4 Extrusion

All heat treated ingots shall be extruded to diameters suitable to comply with Section 102.2.5 under the following conditions:

- a) Extrusion Tooling Temperature - 800 $\pm$ 25°F
- b) Ingots shall be preheated to a uniform temperature of 1125°F, maximum; 1050°F, minimum.
- c) Transfer time from heating medium to the start of the extrusion cycle shall be three (3) minutes, maximum.
- d) Extrusion velocity, defined as the exit speed of the extrusion from the die, shall be between 25 and 50 inches/minute.
- e) Extruded dimensions shall be such that:
 - 1. Not more than 0.250 inch be removed from any OD in machining to a billet core.
 - 2. Not more than 0.250 inch be removed from the ID in machining to the inner tube billet core.
 - 3. Not more than 0.200 inch be removed from the ID in machining to the outer tube billet core.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

3 of 3

DATE

August 9, 1961

SPECIFICATION NO.
CX-102.0 (cont.)

SPECIFICATION TITLE:

URANIUM BILLET FABRICATION (continued)

- f) Maximum clearance between ingot and liner shall not exceed one-half (1/2) inch, based on cold uranium dimensions.
- g) Maximum clearance between ingot ID and mandrel shall not exceed fifty (50) per cent of the mandrel diameter or one-quarter (1/4) inch, whichever is less, based on cold uranium dimensions.
- h) All ingots shall be oriented such that the end toward the top crop passes through the die first.

102.2.5 Machining

The primary extrusions shall be cut to appropriate lengths and machined completely to finished dimensions and surface conditions as called for on Drawings H-3-17076 and H-3-17077, without further working or heat treatment and shall comply with the following two provisions:

- a) At least three (3) inches of full diameter material from the lead end of each primary extrusion shall be cropped and scrapped prior to any billet finishing operations.
- b) Every billet male end shall lie toward the primary extrusion lead end, i.e., the original cast ingot top.

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 3	COPY NO.
	DATE August 9, 1961	
	SPECIFICATION NO. CX-110.0	
SPECIFICATION TITLE: ZIRCALOY CLADDING SHELLS		

110.1 Basis

This specification covers all wrought seamless Zircaloy-2 tubing for use as cladding for coextruded fuel tubes.

110.2 Material Specifications

110.2.1 Chemical Composition

Zircaloy-2 alloy products produced under this specification shall be of the following composition:

a) Alloying Elements

		<u>Weight - Per Cent</u>
Tin	-	1.20 - 1.70
Iron	-	0.07 - 0.20
Chromium	-	0.05 - 0.15
Nickel	-	0.03 - 0.08
Zirconium	-	Remainder, except for normally occurring impurities for which analysis is not otherwise required.

b) Impurity Limits

		<u>PPM - Maximum</u>
Aluminum	-	75
Boron	-	0.5
Cadmium	-	0.5
Carbon	-	500
Cobalt	-	10
Copper	-	50
Hafnium	-	200
Hydrogen	-	50
Lead	-	100
Magnesium	-	20
Manganese	-	50
Molybdenum	-	50
Nitrogen	-	100
Oxygen	-	1400
Silicon	-	100*
Titanium	-	50
Sodium	-	20
Tungsten	-	50
Uranium	-	5
Vanadium	-	50

*250 ppm, maximum, for material derived from Columbia National Sponge.

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. NW-59941	
	PAGE NO. 2 of 3	COPY NO.
	DATE August 9, 1961	
	SPECIFICATION NO. CX-110.0 (cont.)	
SPECIFICATION TITLE: ZIRCALOY CLADDING SHELLS (continued)		

110.2.2 Physical Properties

Zircaloy-2 alloy products produced under this specification shall be in the following physical condition:

a) Grain Size

The metal shall be in the completely recrystallized state or contain a minimum of twenty (20) per cent cold work. The grain size shall not exceed ASTM No. 5 on samples of finished products annealed at 750°C for one (1) hour.

b) Surface Condition

1. All parts shall be free from pressed-in foreign material. Any residual lubricants shall be removable by trichloroethylene degreasing.
2. The inside and outside surfaces of the tubes shall exhibit a surface roughness of not greater than 125 microinches as determined by comparison with ASA B46.1-1955 Standards, or as measured with a profilometer. The surface shall be free of cracks and free of pits that are black in color and/or do not show a visible lustrous, smoothly rounded bottom, or are greater than one-half (1/2) inch in their greatest dimension in the plane of the surface, or greater than 0.003 inch (estimated) in depth.
3. Fluorescent Penetrant Test - All tubes shall be free of all indications when examined on the inside and outside surfaces by means of a fluorescent penetrant technique. The particular technique used shall be Magnaflux Corp. Zyglo-Penetrex ZL-22 (or its equivalent) in accordance with the manufacturer's application specifications. Superficial nicks, scratches, pits or machine marks are acceptable. All cracks, seams, laps, tears, or other defects shall be rejected. Such defects within one-half (1/2) inch of either end shall not be cause for rejection.

110.2.3 Corrosion Properties

Zircaloy-2 alloy products produced under this specification shall pass the following corrosion test:

- a) Samples shall be etched to remove 0.001 to 0.002 inch per surface
- b) Etched samples shall be steam autoclaved at 400°C and 1500 psi for seventy-two (72) hours.
- c) Autoclaved samples shall exhibit a smooth, glossy black finish and have a weight gain of no more than 27 milligrams per square decimeter of exposed surface.

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 3 of 3	COPY NO.
	DATE August 9, 1961	
SPECIFICATION TITLE: ZIRCALOY CLADDING SHELLS (continued)	SPECIFICATION NO. CX-110.0 (cont.)	

110.2.4 Dimensions*

Four tubing sizes are required and are itemized below:

a) Outer Tube, Outer Clad

		<u>Inches</u>
Mean ID	-	6.975 ± 0.005
Wall Thickness	-	0.177 ± 0.005
Ovalness Allowance	-	7.025 Maximum ID 6.925 Minimum ID
Length	-	$19 + 1/64 - 0$
Straightness	-	Maximum uniform bow 0.020 TIR length

b) Inner Tube, Outer Clad

Mean ID	-	5.385 ± 0.005
Wall Thickness	-	0.230 ± 0.005
Ovalness Allowance	-	5.435 Maximum ID 5.335 Minimum ID
Length	-	$19 + 1/64 - 0$
Straightness	-	Maximum uniform bow 0.020 TIR length

c) Outer Tube, Inner Clad

OD	-	2.775 ± 0.005
Wall Thickness	-	0.404 ± 0.005
Ovalness Allowance	-	Within OD tolerance
Length	-	$19 + 1/64 - 0$
Straightness	-	Maximum uniform bow 0.020 TIR length

d) Inner Tube, Inner Clad

OD	-	1.320 ± 0.005
Wall Thickness	-	0.335 ± 0.007
Ovalness Allowance	-	Within OD tolerance
Length	-	$19 + 1/64 - 0$
Straightness	-	Maximum uniform bow 0.020 TIR length

*Note: The dimensional tolerance requirements of this specification (110.2.4) were prepared primarily for procurement. Minor deviations from these requirements, except for wall thickness, shall not be cause for rejection provided satisfactory billet assembly can be carried out and there is no significant effect on the coextruded fuel section dimensional characteristics. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 3

COPY NO.

DATE

November 14, 1961

SPECIFICATION NO.

CX-120.0, Revision 1

SPECIFICATION TITLE:

ZIRCALOY END CAPS

120.1 Basis

This specification presents the material requirements and dimensions for fabricated zircaloy-2 end caps. The outer and inner caps are identical except for OD and ID dimensions.

120.2 Material Specifications

120.2.1 Chemical Composition

Zircaloy-2 products fabricated under this specification shall be of the following composition:

a) Alloying Elements

Weight - Per Cent

Tin	-	1.20 - 1.70
Iron	-	0.07 - 0.20
Chromium	-	0.05 - 0.15
Nickel	-	0.03 - 0.08
Zirconium	-	Remainder

b) Impurity Limits

PPM - Maximum

Aluminum	-	75
Boron	-	0.5
Cadmium	-	0.5
Carbon	-	275
Cobalt	-	10
Copper	-	50
Hafnium	-	200
Hydrogen	-	20
Lead	-	100
Magnesium	-	20
Manganese	-	50
Molybdenum	-	50
Nitrogen	-	50
Oxygen	-	1100
Silicon	-	100*
Sodium	-	20
Titanium	-	50
Tungsten	-	50
Uranium	-	2.5
Vanadium	-	50

*Material derived from Columbia National Sponge shall contain 250 ppm, maximum.

[REDACTED]

DECLASSIFIED

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

2 of 3

DATE

November 14, 1961

SPECIFICATION NO.

CX-120.0, Revision 1

SPECIFICATION TITLE:

ZIRCALOY END CAPS (continued)

120.2.2 Physical Properties

Zircaloy-2 alloy products fabricated under this specification shall be in the following physical condition:

- a) All parts shall be completely deburred.
- b) All parts shall be free from pressed-in foreign material. Any residual lubricants shall be removable by trichlorethylene degreasing.
- c) All surfaces shall be 125 RMS, or better, as determined by comparison with ASA B46.1-1955 Standards, or as measured with a profilometer. The surface shall be free of cracks and free of pits that are dark in color and/or do not show a visible lustrous, smooth rounded bottom or are greater than 0.003 inch (estimated) in depth.
- d) All parts shall be capable of passing, without defect indications, a fluorescent penetrant examination such as Magnaflux Corporation's Zyglo-Penetrex ZL-22 as applied in accordance with the manufacturer's specifications.

120.2.3 Corrosion Properties

Zircaloy-2 alloy products fabricated under this specification shall pass the following corrosion test:

- a) Whole part samples shall be etched to remove 0.001 to 0.002 inch per surface.
- b) Etched samples shall be placed in a steam autoclave at 400°C and 1500 psi for seventy-two (72) hours.
- c) Autoclaved samples shall exhibit a smooth, glossy black finish and have a weight gain of no more than twenty-seven (27) milligrams per square decimeter of exposed surface.

[REDACTED]

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 3 of 3	COPY NO.
	DATE November 14, 1961	
	SPECIFICATION NO. CX-120.0, Revision 1	

SPECIFICATION TITLE:

ZIRCALOY END CAPS (continued)

120.2.4 Dimensions

Caps shall meet dimensional requirements as specified below:

- a) Outer tube end cap per Drawing H-3-17261, Revision 5.
- b) Inner tube end cap per Drawing H-3-17262, Revision 5.

The dimensional tolerance requirements of this specification were prepared primarily for procurement. Minor deviations from these requirements, except for OD and ID diameters, shall not be cause for rejection provided satisfactory bearing can be carried out. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

Approved By: J. M. Gill 2/5/62
Mgr. Coext. Prod. Engr'g-FPD Date

Accepted By: J. W. Nicholas 2/14/62
Mgr. Coextrusion Shop -FPD Date

C. J. Blawie 2/15/62
Mgr. Quality Control -FPD Date

Endorsed By: N. W. Ambrose 2/16/62
Supvr. Reactor Fuels -IPD Date

THIS SPECIFICATION
REPLACES PAGES 1 and 2
DATED 8/9/61

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS		DOCUMENT NO. HW-69941	
SPECIFICATION TITLE: ZIRCONIUM-BERYLLIUM BRAZE ALLOY		PAGE NO. 1 of 2	COPY NO.
		DATE January 9, 1962	
		SPECIFICATION NO. CX-130.0, Revision 2	

130.1 Basis

This specification covers the zirconium-beryllium braze alloy to be used for brazing the zircaloy cap into the recessed ends of the fuel pieces. The alloy used must melt at the specified temperatures so that it will not be necessary to heat the uranium excessively, it must flow freely so that a sound braze is attained, and it must have adequate corrosion resistance to prevent penetration by the reactor process water in case of a defective or damaged weld.

130.2 Specifications

130.2.1 Composition

The braze alloy shall be composed of zirconium and beryllium in the proportions required to approach the lowest possible melting point. The zirconium, or zircaloy (vendor's option) shall be reactor grade and the beryllium shall be equivalent to Brush Beryllium Company QMV grade.

130.2.2 Physical Properties

The brazing alloy shall be in the solid metallic form according to the dimensions specified in Section 130.2.4. The melting point of the alloy shall not exceed 975°C and at this temperature melting shall be complete and uniform with no unmelted particles or pieces remaining. When melted in a vacuum of one micron (10^{-3} mm Hg) or less, the melted alloy shall flow freely with no indications of scum formation or significant dross or residue. Further, upon melting, there shall be no visible bubbling or gas release.

The rings must be received certified clean by the vendor and packaged so as to prevent contamination, or they must be amenable to cleaning by standard trichloroethylene degreasing.

130.2.3 Corrosion Resistance

Pieces of braze alloy subjected to corrosion test of 400°C steam at 1500 psi for seventy-two (72) hours shall show weight gains of not more than thirty (30) milligrams per square decimeter of surface. Such corrosion tested pieces shall exhibit a dull, slate grey to black surface with no white oxide or loose scale.

130.2.4 Dimensions and Weights

The braze alloy rings shall conform to the dimensional and weight requirements of Drawings H-3-17243 and H-3-17244, Revision 2, whichever is applicable.

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 2 of 2	COPY NO.
	DATE January 9, 1962	
	SPECIFICATION NO. CX-130.0, Revision 2	
SPECIFICATION TITLE: ZIRCONIUM-BERYLLIUM BRAZE ALLOY (continued)		

130.2.5 Physical Defects

The rings may contain minor voids or shrinkage cavities, provided such defects are clean and contain no entrapped impurities or foreign material and further provided that such defects do not reduce the cross sectional area of the ring by more than ten (10) per cent. Cracked rings shall be rejected.

The rings shall have a clean metallic surface. Minor specks of graphite imbedded in the cylindrical surfaces shall not be cause for rejection, provided they are no more than 0.050 inch across.

Approved By: S. M. Gill 2/5/62
Mgr. Coext. Prod. Engr'g - FPD Date

Accepted By: J. W. Nielsen 2/14/62
Manager, Coextrusion Shop - FPD Date
Q. R. Blasevich 2/15/62
Manager, Quality Control FPD Date

Endorsed By: J. W. Ambrose 2/16/62
Supervisor, Reactor Fuels- IPD Date

Replaces Page 1 dated
August 9, 1961 and Page 2
dated October 11, 1961

<div style="text-align: center;"> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS </div>	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	1 of 2	
SPECIFICATION TITLE:	DATE	
	August 9, 1961	
	SPECIFICATION NO.	
ZIRCALOY-2 SUPPORTS AND LOCKING DEVICES	CX-140.0	

140.1 Basis

This specification covers the dimensions and material requirements for all co-extruded fuel element supports and locking devices. All supports are fabricated from zircaloy-2. A steel shoe for the outer tube support is covered in Specification CX-160.0.

140.2 Material Specifications

140.2.1 Chemical Composition

Zircaloy-2 products fabricated under this specification shall be of the following composition:

a) Alloying Elements

		<u>Weight - Per Cent</u>
Tin	-	1.20 - 1.70
Iron	-	0.07 - 0.20
Chromium	-	0.05 - 0.15
Nickel	-	0.03 - 0.08
Zirconium	-	Remainder

b) Impurity Limits

		<u>PPM - Maximum</u>
Aluminum	-	75
Boron	-	0.5
Cadmium	-	0.5
Carbon	-	275
Cobalt	-	10
Copper	-	50
Hafnium	-	200
Hydrogen	-	20
Lead	-	100
Magnesium	-	20
Manganese	-	50
Molybdenum	-	50
Nitrogen	-	50
Oxygen	-	1100
Silicon	-	100*
Sodium	-	20
Titanium	-	50
Tungsten	-	50
Uranium	-	2.5
Vanadium	-	50

*250 ppm, maximum for material from Columbia National Sponge

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	2 of 2	
SPECIFICATION TITLE: ZIRCALOY-2 SUPPORTS AND LOCKING DEVICES (continued)	DATE	
	August 9, 1961	
	SPECIFICATION NO. CX-140.0 (cont.)	

140.2.2 Physical Properties

Zircaloy-2 alloy products fabricated under this specification shall be in the following physical condition:

- a) All parts shall be completely deburred.
- b) All parts shall be free from pressed-in foreign material. Any residual lubricants shall be removable by trichloroethylene degreasing.
- c) All surfaces shall be 125 RMS or better, as determined by comparison with ASA-B46.1-1955 Standards. The surface shall be free of cracks and free of pits that are dark in color and/or do not show a visible lustrous, smoothly rounded bottom or are greater than 0.003 inch (estimated) in depth.

140.2.3 Corrosion Properties

Zircaloy-2 alloy products fabricated under this specification shall pass the following corrosion test:

- a) Whole part samples shall be etched to remove 0.001 to 0.002 inch per surface.
- b) Etched samples shall be placed in a steam autoclave at 400°C and 1500 psi for seventy-two (72) hours.
- c) Autoclaved samples shall exhibit a smooth, glossy black finish and have a weight gain of no more than twenty-seven (27) milligrams per square decimeter of exposed surface.

140.2.4 Dimensions*

Two support designs plus a locking device are required.

- a) Outer tube support per Drawing H-3-17183, Revision 3.
- b) Inner tube support per Drawing H-3-17402.
- c) Locking clip per Drawing H-3-17403.

*Note: The dimensional tolerance requirements of this specification (140.2.4) were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided all final support requirements of the finished fuel element supports are met. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

August 9, 1961

SPECIFICATION NO.

CX-160.0

SPECIFICATION TITLE:

STEEL SUPPORT SHOE

160.1 Basis

This specification covers the material and dimensions of the steel shoe that provides the contact surface of the outer tube support.

160.2 Material Specifications

160.2.1 Material

All steel shoes shall be fabricated from steel, flat, cold rolled carbon sheets, special killed, to ASTM A-365-58T.

160.2.2 Dimensions*

All parts shall be fabricated according to Drawing H-3-17183, Rev. 3, Part 3.

160.2.3 Surface Finish

The outer surface which will be in contact with the process tubes shall be 125 RMS or better, as determined by comparison with ASA B46.1-1955 Standards.

160.2.4 Surface Protection

The steel support shoes shall be received and maintained in a rust-free condition. Rust preventative coatings may be used provided they can be removed as specified in Specification CX-250.0.

*Note: The dimensional tolerance requirements of this specification (160.2.2) were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided the shoes can be satisfactorily attached and all final fuel element requirements are met. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing - Quality Control and set forth in the Quality Control Standards.

[REDACTED]

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;"> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS </div>	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	1 of 4	
SPECIFICATION TITLE: COPPER EXTRUSION MATERIALS	DATE	
	October 11, 1961	
	SPECIFICATION NO. CX-170.0, Revision 2	

170.1 Basis

Coextrusion billet assemblies must be protected from contact with extrusion tools during extrusion and sealed against atmospheric contamination while at extrusion preheat temperatures. Either commercially pure copper or silicon-copper alloy components comprise all the extrusion can components.

170.2 Material Specifications

All sleeves and end plates, described below, shall be fabricated from wrought commercially pure copper or a silicon-copper alloy. Different specifications apply for each material. In the section "Dimensions" (170.3), where this choice exists, two ASTM specification numbers are referenced for all except outer sleeves. The first refers to silicon-copper alloys; the second refers to commercially pure standard ASTM products and must be specially specified.

170.2.1 General Chemistry

a) Pure Coppers

All pure copper parts, except preshape cones, shall be of ASTM grade DHP or DLP* copper. For reference, the general composition is listed below:

<u>Element</u>	<u>Weight Per Cent</u>
Copper	99.90, Minimum
Phosphorus	0.015 to 0.040 DHP 0.004 to 0.012 DLP*

b) Silicon-Copper Alloys

All silicon-copper alloy parts shall be of ASTM Alloy A-2 or A-5, as designated in ASTM Specifications B-96, B-97, B-98 and B-99, or Alloy A-7, as designated in ASTM Specification B-315. For reference, the general composition into which these alloys fall is listed below.

<u>Element</u>	<u>Weight Per Cent</u>
Iron	0.25, Maximum
Lead	0.05, Maximum
Manganese	1.35, Maximum
Nickel	0.6, Maximum
Silicon	2.8 to 3.6
Copper	Remainder
Total all above	99.50, Minimum

*Addition of DLP copper

Replaces Page 1 dated 9/14/61

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS		DOCUMENT NO. HW-69941	
SPECIFICATION TITLE: COPPER EXTRUSION MATERIALS (continued)		PAGE NO. 2 of 4	COPY NO.
		DATE September 14, 1961	
		SPECIFICATION NO. CX-170.0 - Rev. 1	

c) Preshape Cone Copper (Forging Copper)

All preshape cones shall be fabricated from ASTM Alloy 12, as designated in ASTM Specification B-124. For reference, the general composition is listed below.

<u>Element</u>	<u>Weight Per Cent</u>
Copper	100 Nominal (99.0, Minimum)

170.2.2 Physical Properties

All products, except preshape cones, supplied under this specification shall be free of cracks, laps, seams, pits, blisters and porosity; they shall also be able to withstand evacuation to 10^{-4} mm of mercury without leaking.

170.3 Dimensions

The dimensional tolerance requirements of this specification were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided satisfactory billet assembly can be carried out and there is no significant effect on the coextruded fuel section dimensional characteristics. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

170.3.1 Outer Tube Billet Components

a) Outer Sleeve

Mean OD	7.500 plus/minus 0.008 inches
Wall	0.063 plus/minus 0.0045 inches
Length	20-3/8 plus 1/64, minus 0 inches
Straightness	1/8 inch maximum bcw per part
Ovalness	Maximum to minimum OD - 1/8 inch maximum

Should these outer sleeves be fabricated by rolling and welding, the following additional specifications shall apply:

Maximum point-to-point wall
variation per part - 0.001 inch maximum

DECLASSIFIED

UNCLASSIFIED

<div style="background-color: black; width: 150px; height: 20px; margin: 0 auto; margin-bottom: 5px;"></div> <p>HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS</p>	<p>DOCUMENT NO. HW-69941</p>		
<p>SPECIFICATION TITLE: COPPER EXTRUSION MATERIALS (continued)</p>	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;">PAGE NO. 3 of 4</td> <td style="width: 50%;">COPY NO.</td> </tr> </table>	PAGE NO. 3 of 4	COPY NO.
	PAGE NO. 3 of 4	COPY NO.	
	<p>DATE October 11, 1961</p>		
<p>SPECIFICATION NO. CX-170.0, Revision 2</p>			

b) Inner Sleeve (ASTM B-315 or B-75)

OD	1.930 ± 0.004 inches
Wall	0.065 ± 0.005 inches
Length	20-3/8 + 1/64, - 0 inches

c) Front End Plate (ASTM B-97 or B-152)

Dimensions per Drawing H-3-17077, Sheet 5, Revision 4, Detail 7, "Front End Cap".

d) Rear End Plate (ASTM B-97 or B-152)

Dimensions per Drawing H-3-17077, Sheet 5, Revision 4, Detail 8, "Rear End Caps".

e) Preshape Nose Cone (ASTM B-124)

Dimensions per Drawing H-3-17077, Sheet 4, Revision 0, Detail 5, "Nose Cone".

f) Preshape Rear Cone (ASTM B-124)

Dimensions per Drawing H-3-17077, Sheet 4, Revision 0, Detail 6, "Rear Cone".

g) Evacuation Tube (ASTM B-75)

OD	0.375 ± 0.002 inches
Wall	0.065 ± 0.003 inches
Length	6-1/2 ± 1/4 inch

170.3.2 Inner Tube Billet Components

a) Outer Sleeve (---ASTM B-75)

Mean OD	6.000 ± 0.008 inches
Wall (Cu-Si)	0.063 ± 0.0045 inches
Wall (B-75)*	0.065 ± 0.008 inches
Length	20-5/8 + 1/64, - 0 inches
Straightness	1/8 inch maximum bow per part
Ovalness	Maximum to minimum OD - 1/8 inch maximum

Should these outer sleeves be fabricated by rolling and welding, the following additional specifications shall apply.

Maximum point-to-point wall
variation per part - 0.001 inches maximum

*Addition of (B-75)

Replaces Page 3 dated 9/14/61

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

4 of 4

COPY NO.

DATE

October 11, 1961

SPECIFICATION NO.

CX-170.0, Revision 2

SPECIFICATION TITLE:

COPPER EXTRUSION MATERIALS (continued)

b) Inner Sleeve (ASTM B-315 or B-75)

OD	0.625 ± 0.0025 inches
Wall	0.065 ± 0.0045 inches
Length	20-5/8 + 1/64, - 0 inches

c) Front End Plate (ASTM B-97 or B-152)

Dimensions per Drawing H-3-17076, Sheet 5, Revision 4, Detail 7, "Front End Cap".

d) Rear End Plate (ASTM B-97 or B-152)

Dimensions per Drawing H-3-17076, Sheet 5, Revision 4, Detail 8, "Rear End Cap".

e) Preshape Nose Cone (ASTM B-124)

Dimensions per Drawing H-3-17076, Sheet 4, Revision 0, Detail 5, "Nose Cone".

f) Preshape Rear Cone (ASTM B-124)

Dimensions per Drawing H-3-17076, Sheet 4, Revision 9, Detail 6, "Rear Cone".

g) Evacuation Tube (ASTM B-75)

OD	0.375 ± 0.002 inches
Wall	0.065 ± 0.003 inches
Length	6-1/2 ± 1/4 inch

Approved By:

S. M. Giee

Mgr. Coext. Prod. Engr'g - FPD

10/17/61
Date

Accepted By:

J. W. Huls

Mgr. Coextrusion Shop - FPD

10/20/61
Date

C. H. Blawie

Mgr. Quality Control - FPD

11/14/61
Date

Endorsed By:

A. W. Ambrose

Supvr. Reactor Fuels - IPD

11/15/61
Date

DECLASSIFIED

Replaces page 4 dated
9/14/61

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HW-69941

PAGE NO. COPY NO.
1 of 1

SPECIFICATION TITLE:

TOOL DESIGNS AND PREPARATION

DATE
August 9, 1961

SPECIFICATION NO.
CX-180.0

180.1 Basis

Inasmuch as the coextrusion process requires tools which are much more precisely made and closely controlled than those in normal extrusion practice, it is required that specifications for those items which are critical be established.

180.2 Specifications

180.2.1 Mandrels*

The mandrels used for the coextrusion process shall be as shown on the following drawings:

H-3-17301 - NOT, Travelling Mandrel
H-3-17302 - NOT, Free Mandrel
H-3-17303 - NIT, Travelling Mandrel
H-3-17304 - NIT, Free Mandrel

Exact diametral dimensions may be established, or changed, to give extrusions more closely meeting the requirements of subsequent specifications.

180.2.2 Dies*

The dies used for the coextrusion process shall be as shown on the following drawings:

H-3-17305 - NOT
H-3-17306 - NIT

Exact throat dimensions may be established, or changed, to give extrusions more closely meeting the requirements of subsequent specifications.

180.2.3 Containers & Liners

The container and liner assemblies are considered to be engineered equipment and prior to replacement or procurement of new assemblies, the drawings and specifications shall be reviewed by the appropriate Engineering personnel.

180.2.4 Tool Conditioning

All new or reground tooling shall be preconditioned prior to use by thoroughly degreasing in trichloroethylene vapors and holding at 800°F for at least four (4) hours to form an oxide coating.

*Note: The dimensional tolerance requirements of these specifications (180.2.1 & 180.2.2) were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided the final fuel element meets all dimensional requirements of these specifications. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing-Quality Control and set forth in the Quality Control Standards.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

January 29, 1962

SPECIFICATION NO.

CX-190.0, Revision 1

SPECIFICATION TITLE:

EXTRUSION CUT-OFFS

190.1 Basis

An extrusion cut-off is used to allow extrusion of all billet material through and clear of the die and to clear the mandrel from the extrusion.

190.2 Material Specifications

All graphite components are non-critical regarding composition and virtually all electrode-type graphites are acceptable. Specific manufacturers products that have proven acceptable are listed below:

- a) International Graphite Type 3474, mold type electrodes
- b) Crescent Grade CMD
- c) Great Lakes Grade HCM
- d) National CS Graphite Rods
- e) Speer Grade 890-S

190.3 Dimensions*

190.3.1 Outer Tube Billet

Dimensions per Drawing H-3-16912, Revision 2, Part 1

190.3.2 Inner Tube Billet

Dimensions per Drawing H-3-16910, Revision 2, Part 1

* Note: The dimensional tolerance requirements of this specification (190.3) were prepared primarily for procurement. Minor deviations from these requirements shall not be cause for rejection provided the coextrusion operation can be carried out satisfactorily. The degree of inspection required, the methods of inspection, and specific dimensional tolerances to be used internally as rejection limits shall be determined by Manufacturing Quality Control and set forth in the Quality Control Standards.

Approved By: Sam Gill 2/5/62
Mgr. Coext. Prod. Engineering - FPD Date

Accepted By: JW Kukulski 2/14/62
Manager, Coextrusion Shop - FPD Date
W. Bleswick 2/15/62
Manager, Quality Control - FPD Date

Endorsed By: W. Ambrose 2/16/62
Supervisor, Reactor Fuels - IPD Date

Replaces Specification
dated August 9, 1961

[REDACTED]

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 1

DATE

August 9, 1961

SPECIFICATION NO.

CX-201.0

SPECIFICATION TITLE:

URANIUM BILLET CLEANING AND INSPECTION

201.1 Basis

The uranium billets are cleaned and etched to give a surface free of oxides and foreign materials to insure bonding during coextrusion. They are also inspected to detect any physical flaws which would adversely affect the coextruded product.

201.2 Specifications

- 201.2.1 Only billets meeting the requirements of Specifications CX-101.0 and CX-102.0 and Drawings H-3-17076 or H-3-17077, whichever is applicable, shall be processed for extrusion.
- 201.2.2 All uranium billets shall be cleaned by degreasing in trichloroethylene vapor, etched in warm nitric acid and rinsed and dried to give a surface free of all objectionable foreign material and oxide.
- 201.2.3 The prepared billets shall be inspected for fabrication flaws and shall meet the requirements set forth in Specification CX-101.2.4. Any billet which becomes re-oxidized to where it shows oxide color darker than a light golden shall be re-etched. Billets may not be processed more than three (3) times.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

August 9, 1961

SPECIFICATION NO.

CX-210.0

SPECIFICATION TITLE:

ZIRCALOY CLADDING COMPONENT CLEANING AND INSPECTION

210.0 Basis

The zircaloy cladding components are cleaned to assure satisfactory bonding between the uranium and zircaloy during coextrusion. They are inspected for flaws which might affect product quality.

210.2 Specifications

- 210.2.1 The zircaloy cladding components used in the coextrusion process shall conform to the requirements of Specification CX-110.0.
- 210.2.2 The cladding components shall be thoroughly cleaned by degreasing in trichloroethylene vapors and washing in a hot detergent solution such as Alconox 403. They shall be hot rinsed to remove all cleaning materials and air dried.
- 210.2.3 The cleaned components shall be inspected for manufacturing flaws and shall meet the requirements of Specification CX-110.0. However, minor defects may be removed by light sanding, provided the dimensional requirements of Specification CX-110.0 are not violated.

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO.	
	HW-69941	
	PAGE NO. 1 of 1	COPY NO.
SPECIFICATION TITLE: ZIRCALOY END CAP CLEANING AND INSPECTION	DATE August 9, 1961	
	SPECIFICATION NO. CX-220.0	
<p>220.1 <u>Basis</u></p> <p>The end caps must be thoroughly cleaned to insure wetting and bonding during the brazing operation. They are also inspected to eliminate those caps which would give faulty closures.</p> <p>220.2 <u>Specifications</u></p> <p>220.2.1 Only caps meeting the requirements of Specification CX-120.0 and Drawings H-3-17261 or H-3-17262 shall be used in the closure operation.</p> <p>220.2.2 The end caps shall be cleaned by first degreasing in trichloroethylene vapors and then etching in nitric-hydrofluoric acid solution. Etching shall be sufficient to remove between one (1) mil and two (2) mils of metal per surface. Etched caps shall be adequately rinsed and dried to give surfaces free of all etchants or other foreign material.</p> <p>220.2.3 The caps shall be inspected to insure that the cleaning has been effective, as evidenced by a bright specular surface.</p>		

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 1	COPY NO.
	DATE August 9, 1961	
	SPECIFICATION NO. CX-230.0	
SPECIFICATION TITLE: BRAZE ALLOY CLEANING AND INSPECTION		

230.1 Basis

The zirconium-beryllium alloy used to effect the brazed closure must be clean and free of foreign material which will affect the quality of the closure. The braze rings must also be inspected for cracks or other physical defects which will affect the manner in which they melt and flow.

230.2 Specifications

230.2.1 The alloy rings used in the brazing operation must meet the requirements of Specification CX-130.0 and Drawing H-3-17243 or Drawing H-3-16244, whichever is applicable.

230.2.2 The braze alloy rings shall be thoroughly cleaned by degreasing in trichloroethylene vapors.

230.2.3 The cleaned rings shall be inspected for cracks or other physical defects which would affect the manner in which they melt, and also for any sign of casting skin or other mold materials; such defective rings shall be rejected.

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	1 of 1	
SPECIFICATION TITLE: ZIRCALOY SUPPORT AND LOCKING DEVICE CLEANING AND INSPECTION	DATE	
	August 9, 1961	
	SPECIFICATION NO. CX-240.0	

240.1 Basis

The zircaloy supports and locking devices must be adequately cleaned so that they can be satisfactorily welded to the clad fuel pieces without adversely affecting the integrity of the fuel in any way.

240.2 Specifications

240.2.1 All fuel element supports and locking devices used shall meet the requirements of Specification CX-140.0 and Drawing H-3-17183, Rev. 3, or Drawing H-3-17042, or Drawing H-3-17043, whichever is applicable.

240.2.2 The supports and locking devices shall be cleaned by first degreasing in trichloroethylene vapors and then etching in nitric-hydrofluoric acid solution. Metal removal shall not exceed 0.0005 inch, but shall be sufficient to remove all oxide. Etched surfaces shall be adequately rinsed and dried to remove all etchants and other foreign material.

240.2.3 The cleaned parts shall be inspected to insure that the cleaning has been effective and that defective material is eliminated.

<div style="text-align: center;"> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS </div>	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	1 of 1	
SPECIFICATION TITLE:	DATE	
STEEL SUPPORT SHOE CLEANING AND INSPECTION	August 10, 1961	
	SPECIFICATION NO. CX-250.0	

250.1 Basis

The support shoes must be cleaned of any material which would affect their corrosion resistance during storage or irradiation, affect the corrosion resistance of the zircaloy support, or contaminate the reactor process water. They must also be inspected to eliminate defects which would prevent them from serving their intended purpose.

250.2 Specifications

- 250.2.1 All support shoes shall meet the requirements of Specification CX-150.0 and Drawing H-3-17183, Revision 3, Part 3.
- 250.2.2 The support shoes shall be thoroughly cleaned of all foreign material by degreasing in trichloroethylene vapors. They shall be inspected for any manufacturing or material defects which would render them unfit for use.

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 1

DATE

September 1, 1961

SPECIFICATION NO.

CX-270.0 Revision 1*

SPECIFICATION TITLE:

COPPER COMPONENTS - CLEANING AND INSPECTION

270.1 Basis

The copper components used to make up the evacuation cans must be cleaned of all foreign material and oxide, particularly on those surfaces next to the uranium and zircaloy, so that the billet components will not be contaminated during heating. Copper materials containing inclusions or impurities which would outgas during heating must be rejected.

270.2 Specifications

270.2.1 All copper, or copper-silicon alloy components used in the extrusion operation shall comply with the requirements of Specification CX-170.0.

*270.2.2 All copper, or copper-silicon alloy components shall be prepared for use by degreasing in trichloroethylene vapors and etching in nitric acid and/or "Zinctone" followed by adequate rinsing to remove all reagents or reagent salts.

270.2.3 The cleaned and etched components shall exhibit a bright clean surface without significant stains or residual oxides. They shall be inspected for inclusions or fabrication defects which could outgas during heating or in any other way adversely affect the quality of the extruded product.

Approved by: S.M. Gile
Mgr. Coextr. Prod. Engr.-FPD

Endorsed by: V. Wambse
Supvr. Reactor Fuels -IPD

Accepted by: J. M. H. [Signature]
Mgr. Coextrusion Shop -FPD
[Signature]
Mgr. Quality Control -FPD

Replaces page dated 8/10/61

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS		DOCUMENT NO. HW-69941	
		PAGE NO. 1 of 2	COPY NO. 24
SPECIFICATION TITLE: BILLET ASSEMBLY		DATE February 26, 1962	
		SPECIFICATION NO. CX-301.0, Revision 1	
<p>301.1 <u>Basis</u></p> <p>During the coextrusion process, the uranium fuel is clad with zircaloy as the two metals are extruded together under the proper pressure and temperature conditions. Since uranium and zircaloy both react vigorously with the atmosphere at the required extrusion temperatures, it is necessary that the billets be canned and evacuated to prevent reaction with the atmosphere while being heated. Copper, or copper alloys, are generally used for evacuation cans since copper is less prone to gall on the extrusion dies than most metals, and it can also be removed from the extruded tubes by etching in nitric acid. Briefly, billet assembly consists of placing zircaloy sleeves both in and around the uranium billet and placing this assembly in a copper can which is welded shut, evacuated and leak tested.</p> <p>301.2 <u>Specifications</u></p> <p>301.2.1 <u>Component Assembly</u></p> <ul style="list-style-type: none">a) The components shall be assembled without the use of undue force. Some ovality of the clad or copper can be accommodated by springing. Any indications that any of the components have been damaged by denting, scratching, galling or buckling shall be cause for disassembly and inspection. Disassembled components shall be rejected if they no longer meet the requirements of Sections 100 and 200.b) During assembly, all components shall be protected from contamination of all kinds. Billet cores which exhibit reoxidation, as indicated by colors darker than light golden, shall be re-etched before assembly.c) After insertion of all components into the copper can and before fitting of the front end cap, the distance from the top surface of the nose cone to the top of the copper can wall shall be at least 9/16 inch, but not over 11/16 inch. <p>*301.2.2 <u>Evacuation Can Welding</u></p> <ul style="list-style-type: none">a) The evacuation tube shall be welded to the end plate and the end plates welded to the can using the tungsten-inert gas process with argon, argon-helium mixture, or helium as the protecting atmosphere.b) Fit-up of the components and welding parameters, such as amperage, speed, and electrode spacing shall be selected to insure sound, strong welds with adequate penetration to prevent leakage or cracking. Further, to prevent poor bonding in the usable part of the extrusion, the weld heat input shall be controlled such that uranium and zircaloy surfaces are not adversely affected by welding.c) The welds produced shall be uniform in appearance, smooth, free of craters, voids, cracks and porosity. Any evidence of boiling, bubbling, or blowing out during formation of the welds shall be cause for rejection.d) After the bottom has been welded to the can, and before assembly of the uranium and zircaloy components, the bottom weld shall be leak tested. The can shall be placed in an appropriate fixture and			

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

2 of 2

COPY NO.

DATE

February 26, 1962

SPECIFICATION NO.

CX-301.0, Revision 1

SPECIFICATION TITLE:

BILLET ASSEMBLY (continued)

evacuated to 1×10^{-3} mm or less and checked for leaks with a helium leak detector. Any leaks found may be marked and rewelded.

- e) Weld bead overhang shall not increase the OD by more than 0.030 inch or decrease the ID by more than 0.020 inch.

301.2.3 Billet Evacuation

- a) Immediately after welding of the top cap, the billet shall be helium leak tested. Leaking welds may be repaired.
- b) The total elapsed time from assembly of the uranium and zircaloy components until satisfactory leak test has been finished shall not exceed one (1) hour, and the total elapsed time from finish of uranium billet pickle shall not exceed two (2) hours.
- c) Total evacuation time at a manifold pressure of 1×10^{-4} mm Hg or less shall be at least one (1) hour after completion of a satisfactory leak test.
- d) After the evacuation period specified in Section 301.2.3 (a), the evacuation tube shall be flattened and sealed off in such a manner as to preclude the loss of vacuum in the billet.

Approved By:

S. M. Glee 2/28/62
Mgr.-Coext. Product Engr'g - FPD Date

Accepted By:

J. W. Nicholas 2/28/62
Manager - Coextrusion Shop - FPD Date

W. B. Blum 3/1/62
Manager - Quality Control - FPD Date

Endorsed By:

A. W. Ambrose 3/2/62
Supervisor - Reactor Fuels - IPD Date

*Requirement that weld penetration be equal or greater than can wall thickness was deleted.

Replaces Specification
dated August 10, 1961.

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HW-69941

PAGE NO. COPY NO.
1 of 1 A24

SPECIFICATION TITLE:

BILLET PRE-EXTRUSION LUBRICATION

DATE
January 15, 1962

SPECIFICATION NO.
CX-401.0, Revision 2

401.1 Basis

The success of the coextrusion process depends entirely on the smooth, uniform flow of the material being extruded through the conical die in a streamlined fashion. Any deviation from such condition, such as galling or pickup on the container or die, will result in a faulty product. Copper is used to encase the zircaloy and uranium because it will flow as desired without galling or pickup, provided it is properly lubricated. Since the extrusion process is carried out relatively hot, 1170°F, it is necessary that the material used retains its lubricating properties at this temperature. Graphite, applied in the colloidal form, meets the requirements satisfactorily.

401.2 Specifications

- 401.2.1 After evacuation and before lubrication, the billets shall be degreased in trichloroethylene vapors for sufficient time to remove all grease, oil, fingerprints, etc. which may be on the billets.
- 401.2.2 The billets shall be lubricated on all surfaces with Aqua-dag by brushing or dipping. The Aqua-dag may be thinned with one part water to one part Aqua-dag (or alcohol for quick drying to facilitate application.
- *401.2.3 The billet shall have a smooth, even coat of lubricant with no lumps or foreign material visible. If the billet shows any area where the lubrication has flaked off, this area shall be thoroughly cleaned and re-lubricated.

Approved By: S. M. Gill
Mgr., Coextrusion Product Engr'g - FPD

2/21/62
Date

Accepted By: J. W. Nicholas
Manager, Coextrusion Shop - FPD

2/21/62
Date

A. J. Blawie
Manager, Quality Control - FPD

2/22/62
Date

Endorsed By: A. W. Ambrose
Supervisor, Reactor Fuels - IPD

2/26/62
Date

Replaces Specification
(Revision 1) dated
September 15, 1961

*Previous specification required drying.

[REDACTED]
HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

February 19, 1962

SPECIFICATION NO.

CX-410.0, Revision 2

SPECIFICATION TITLE:

BILLET PREHEAT

410.1 Basis

The composite billets must be preheated to match more closely the extrusion characteristics of the component materials, promote bonding between the zircaloy and the uranium, and to reduce the forces required to flow the materials through the die. The quality of the extrusion, as indicated by the concentricity, roundness, straightness and uniformity of clad is extremely dependent upon the uniformity of the billet temperature at the time of extrusion. To assure the required uniformity, the billet is allowed to soak at temperature for a reasonable length of time.

Preheating must be done under such conditions as to result in a surface on the copper which will not pickup or gall on the tools.

410.2 Specifications

*410.2.1 The billet shall be enclosed in a stainless steel can with a tightly fitted lid. The inside of the stainless steel can shall be clean to prevent excessive oxidation of the copper extrusion can and to prevent pickup of foreign material such as scale, graphite, metal chips, etc.

**410.2.2 The billets shall be loaded with the evacuation tube up, with special care being taken to avoid damage to billet lubrication. A graphite disc or graphite cutoff of the proper size shall be placed in either the bottom or the top of the stainless steel can. The can lids shall be close fitting with no evidence of warp or misfit.

410.2.3 The NOT billets shall be heated to $1170^{\circ}\text{F} \pm 15$ degrees, and the NIT billets shall be heated to $1140^{\circ}\text{F} \pm 15$ degrees, and they shall be soaked at this temperature for at least twenty (20) minutes. Billet heating may be accelerated by loading into a "hot zone" where the temperature is above 1170°F , but not over 1300°F . Billets shall be spaced so that the cans are at least one (1) inch from each other and one (1) inch from any other surface.

At no time shall any of the composite billet components exceed the uranium alpha-beta transformation point of 1220°F .

Approved By: S. M. Jice
Mgr. Coext. Product Engr'g - FPD

2/21/62
Date

Accepted By: J. W. Kholars
Manager, Coextrusion Shop - FPD

2/21/62
Date

C. J. Blasewitz
Manager, Quality Control - FPD

2/22/62
Date

Endorsed By: A. W. Ambrose
Supervisor, Reactor Fuels - IPD

2/26/62
Date

*Previously required Aqua-dag recoating.

**Changes graphite disc position requirement.

Replaces Specification
(Revision 1) dated
October 24, 1961

[REDACTED]
DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

SPECIFICATION TITLE:

TOOL CLEANING, PREHEAT AND LUBRICATION

DATE

October 24, 1961

SPECIFICATION NO.

CX-420.0, Revision 1

420.1 Basis

The allowable tolerances in wall thickness, ovality, clad thickness, etc., of the coextruded fuel tubes are much less than those usually allowed in commercial extrusion practice. In order to meet these tolerances, or possibly better them, it will be necessary to provide and maintain the press tooling in the best possible condition. Excessive wear, pickup or lack of lubrication will seriously affect the product quality.

420.2 Specifications

420.2.1 The tools used and their preconditioning shall be as specified in Specification CX-180.0.

420.2.2 Between each extrusion, the tools shall be inspected for mechanical damage, such as nicks, scratches, bending, etc, and for galling or pickup. Damaged tools shall be reconditioned or discarded. All copper or zircaloy pickup shall be completely removed by wire brushing.

*420.2.3 All tools except the NIT mandrel shall be preheated to $800^{\circ}\text{F} \pm 25^{\circ}$ prior to lubrication and maintained at that temperature as nearly as practical until use. The NIT mandrels shall be lubricated and used at room temperature.

420.2.4 All tools shall be lubricated immediately before use in such manner as to give complete protection from pickup and galling during the extrusion. The lubricant shall contain no foreign material or dry hard lumps which would in any way affect the quality of the product.

*Section revised.

Approved By: S.M. Gill by A.E. Buay 10-26-61
Mgr. Coext. Prod. Engr. - FPD Date

Accepted By: J. W. Nicholas 10/26/61
Mgr. Coextrusion Shop FPD Date
C. R. Blawie 11/8/61
Mgr. Quality Control FPD Date

Endorsed By: V. W. Ambrose 11/15/61
Supervisor, Reactor Fuels-IPD Date

Replaces Specification
dated August 10, 1961

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HW-69941

PAGE NO. COPY NO.
1 of 1

SPECIFICATION TITLE:

CUTOFF PREPARATION AND PREHEAT

DATE
January 24, 1962

SPECIFICATION NO.
CX-430.0, Revision 1

430.1 Basis

A cutoff disc is required to push the extreme rear end of the billet through the conical die and thereby free it for transfer to the runout table. Graphite serves this purpose satisfactorily and is less expensive than copper.

430.2 Specifications

430.2.1 The graphite cutoff used shall meet the requirements of Specification CX-190.0.

430.2.2 The inner tube graphite cutoff shall be heated with the tooling to a temperature of $800 \pm 25^{\circ}\text{F}$. The outer tube cutoff shall be heated to $1170 \pm 25^{\circ}\text{F}$ with the billet.

Approved By: S. M. Gie
Mgr. Coextruded Product Engr'g - FPD

1/24/62
Date

Accepted By: J. H. Nicholas
Manager, Coextrusion Shop - FPD

1/24/62
Date

A. J. Blawie
Manager, Quality Control - FPD

1/24/62
Date

Endorsed By: N. W. Ambrose
Supervisor, Reactor Fuels - FPD

1-29-62
Date

Replaces Specification dated
August 10, 1961

[REDACTED]

DECLASSIFIED

DECLASSIFIED

<div style="background-color: black; width: 150px; height: 20px; margin: 0 auto; margin-bottom: 5px;"></div> <p>HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS</p>	<p>DOCUMENT NO. HW-69941</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%;">PAGE NO. 1 of 1</td> <td style="width: 50%;">COPY NO.</td> </tr> </table> <p>DATE January 9, 1962</p> <p>SPECIFICATION NO. CX-450.0, Revision 1</p>	PAGE NO. 1 of 1	COPY NO.
PAGE NO. 1 of 1	COPY NO.		
<p>SPECIFICATION TITLE:</p> <p style="text-align: center;">EXTRUSION OPERATION</p>			

450.1 Basis

The composite billet assembly is converted into a zircaloy clad uranium fuel tube by the extrusion operation. The quality of the extruded tube is dependent upon many things, not the least of which is the skill, care, effort, and precision which are put into the extrusion effort. The billet handling must be such as to minimize the time elapsed between removal from the preheat furnace and the extrusion operation so that the billet will be at uniform temperature when extruded. The chances of billet damage, particularly breaking of the copper can, must be reduced to the lowest practical, and the extrusion press must be so aligned and operated that it will not produce tubes which are unacceptable because of dimensional variations.

450.2 Specifications

- 450.2.1 All tools in contact with the billet before and during the extrusion shall be heated and lubricated as specified in Specification CX-420.0, Revision 1.
- 450.2.2 The total elapsed time for removal of the billet from the furnace until insertion into the liner and upset shall not exceed three (3) minutes. The follower blocks and NOT free mandrels shall not be allowed to cool more than five (5) minutes before use. The NOT traveling mandrel temperature shall not be less than 775°F just prior to extrusion.
- 450.2.3 The billet shall be visually inspected for handling damage while on the loader. Any indication that the can has been ruptured shall be cause for rejection.
- 450.2.4 Extrusion velocity, defined as exit speed of the extrusion from the die, shall be within a range of 230-270 inches per minute. A permanent recording of ram speed and extrusion pressure shall be made and identified for each extrusion.
- 450.2.5 The extruded tube shall be rolled continuously on the runout table for ten (10) minutes, or until its temperature has dropped below 500°F.

Failure to meet this requirement shall not be cause for rejection, but the fact shall be recorded for future reference.

Approved By: Sam. Gill 1/24/62
Mgr. Coext. Prod. Engr. - FPD Date

Accepted By: J. W. Nicholas 1/24/62
Manager, Coextrusion Shop-FPD Date

W. H. Blum 1/26/62
Manager, Quality Control -FPD Date

Endorsed By: W. Ambrose 1-30-62
Supervisor, Reactor Fuels-IPD Date

Replaces Specification
dated August 10, 1961

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HN-66941

PAGE NO. 1 of 1	COPY NO.
--------------------	----------

SPECIFICATION TITLE:

EXTRUDED TUBE SECTIONING

DATE

August 10, 1961

SPECIFICATION NO.
CX-501.0

501.1 Basia

The coextrusion process, as developed for use in the manufacture of NPR fuel elements, is based on the practicality of cutting long extrusions into relatively short sections and subsequently closing these sections to form elements. The sectioning step is critical in that it is necessary that the pieces be cut to exactly the right length, that they be cut square and that they not be damaged in any manner. Also, sufficient material must be cropped from each end of the extrusion to give the required quality in all pieces subsequently processed.

501.2 Specifications

- 501.2.1 The extrusions shall be handled between extrusion and sectioning with sufficient care that they shall not be marred or bent.
- 501.2.2 The ends of the fuel sections shall be normal to the axis of the tube to within 0.25 degree. They shall be free of smeared zircaloy and shall have a surface roughness of not over 125 microinches. (ASA B46.1-1955).
- 501.2.3 Sufficient cropping shall be done to insure that all material meets the dimensional tolerances as specified in Specification CX 660.0.

DECLASSIFIED

UNCLASSIFIED

R.D. Complete 3.2.7.5

505.2.1 THE AS-SECTIONED FUEL ELEMENTS MUST BE CLEANED TO COMPLETE REMOVAL OF ALL EXTRUSION RESIDUES OR FOREIGN MATERIALS WHICH MASK COPPER FROM ACID ATTACK. CHEMICAL CLEANING METHODS (UNION DEGREASE, HOT ALKALINE DETERGENTS) MAY BE SUPPLEMENTED BY MECHANICAL METHODS (ABRASIVE BLASTING, WIRE BRUSHING) THAT DO NOT EXPOSE ZIRCONIUM-2 CLADDING DURING THE CLEANING PROCESS.

505.2.2 THE COPPER SHALL BE REMOVED WITH NITRIC ACID. CARE SHALL BE TAKEN TO ASSURE THAT ALL VISIBLE PARTICULATE COPPER IS REMOVED. ACID SOLUTION COMPOSITIONS AND COMPOSITIONS SHALL BE CONTROLLED TO PROVIDE RAPID COPPER REMOVAL TO MINIMIZE ACID ATTACK ON THE EXPOSED URAMIUM CORE.

505.2.3 THE FUEL SECTIONS SHALL BE RINSED IN PROCESS WATER AND INSPECTED FOR COMPLETION OF COPPER REMOVAL. FUEL SECTIONS WITH ~~RESIDUAL VISIBLE COPPER~~ SHALL NOT BE PROCESSED THROUGH NITRIC HYDROFLUORIC ETCHANT UNTIL FREE OF VISIBLE PARTICULATE COPPER.

UNCLASSIFIED

CONFIDENTIAL

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

SPECIFICATION TITLE:

COPPER REMOVAL

DATE

October 11, 1961

SPECIFICATION NO.

CX-505.0, Revision 1

505.1 Basis

Once the extrusion has been made and the tube sectioned, the copper jacket, which was the evacuation can, has no further use and must be removed before subsequent processing of the tube sections. Although the copper is only partially bonded to the Zircaloy, it is not possible to strip it off mechanically. It is most easily removed by dissolution in ~~warm~~ nitric acid.

505.2 Specifications *During extrusion process is dissolved into the Zircaloy and will not be removed in this process. Sufficient Zircaloy clad is removed in pre-etch to clean to remove the copper dissolved jacket.*

505.2.1 The as-sectioned fuel elements shall be cleaned to remove excess lubricant, cutting oil, grease, and any other foreign material. This shall be done by scrubbing in hot detergent and/or vapor degreasing in trichloroethylene.

505.2.2 The copper shall be removed by dissolution in ~~warm~~ nitric acid. Care shall be taken to assure that all minute specks and particles of pure copper are removed. Acid conditions and compositions shall be controlled to minimize any tendency for the copper to back-plate on the zircaloy.

505.2.3 The fuel sections shall be rinsed in process water and inspected for completion of copper removal. Pieces not completely free of copper shall be re-etched as in Section 505.2.2

Approved By: *S.M. Gile*
Mgr. Coext. Prod. Engr'g-FPD

10/17/61
Date

Accepted By: *J. W. Kerkhofs*
Mgr. Coextrusion Shop -FPD

10/20/61
Date

A. J. Blum
Mgr. Quality Control -FPD

11/14/61
Date

Endorsed By: *A. W. Ambrose*
Supvr. Reactor Fuels -IPD

11/15/61
Date

DECLASSIFIED

Replaces Specification
dated 8/10/61

DECLASSIFIED

RD Sample 7-27-62

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 1	COPY NO.
	DATE January 29, 1962	
	SPECIFICATION NO. CX 515.0, Revision 1	

SPECIFICATION TITLE:
END CLOSURE RECESSING

515.1 Basis

The coextrusion cladding process, as developed for use at HAP0, requires that the fuel elements be made by closing the ends of sections cut from relatively long coextruded tubes. Heat transfer considerations require that the cap or end closure be at least 0.20 inches thick. In order to provide this cap thickness, and at the same time keep the mating of the clad and cap as far from the uranium as possible, it is necessary to recess the uranium so that the cap fits down between the outer and inner clad. The closure is then made at the extremity of the clad. This required recessing is best done by dissolving away the required uranium without attacking the clad. The relative thinness of the clad and the fact that the tubes may be slightly oval, or eccentric, makes it impractical to remove the uranium completely by machining.

515.2 Specifications

515.2.1 The uranium shall be removed by dissolution in $\text{CuSO}_4\text{-HNO}_3\text{-H}_2\text{SO}_4$ solution. The solution composition and temperature shall be such that the dissolution rate shall be approximately 0.0015 inch per minute and shall give a surface free of objectionable pitting and within the dimensional limits listed below.

515.2.2 The recess produced shall be 0.310 ± 0.010 inch deep, as measured by a ring gauge slightly smaller than the caps. Surface variations shall not exceed 0.020 inch, exclusive of discrete individual pits which may be up to 0.050 inch across and 0.020 inch deep. There shall not be more than twenty-five (25) such pits per end. There shall be no visible evidence of bond line undercutting or attack.

515.2.3 There shall be 100% inspection of recesses to assure proper depth.

Approved By: S. M. Gill 2/15/62
Mgr., Coextrusion Product Engr'g - FPD Date

Accepted By: J. W. Whirlman 2/19/62
Manager, Coextrusion Shop - FPD Date
A. B. Brown 2/19/62
Manager, Quality Control - FPD Date

Endorsed By: A. W. Whitman 2/21/62
Supervisor, Reactor Fuels - IPD Date

Replaces Specification
dated August 10, 1961.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69541

PAGE NO.

COPY NO.

1 of 1

DATE

November 14, 1961

SPECIFICATION NO.

CX-520.0, Rev. 1

SPECIFICATION TITLE:

PRE-BRAZE CLEANING

520.1 Basis

The clad surface exposed by the chemical dissolution of the uranium is normally contaminated with a layer of uranium-zirconium compounds plus any impurities or foreign material which may have been present in the interface. This must be removed to promote wetting of the clad by the molten braze alloy and also to prevent contamination of the braze layer by uranium. This is done by etching the zircaloy in nitric-hydrofluoric acid solution. Also, the recessed uranium must be cleaned of all traces of oxide and fluorides to promote bonding of the braze and the uranium and to prevent fluoride contamination of the final weld which might affect its corrosion resistance.

520.2 Specifications

- 520.2.1 The chemically milled pieces shall be rinsed in hot process water and transferred without drying to the initial zircaloy etch bath. They shall be etched to remove from 0.001 to 0.0015 inch per surface. The etching shall be done with vigorous agitation of the pieces and/or bath, with particular care to insure that the inner clad is etched uniformly and completely.
- 520.2.2 The etched pieces shall be rinsed in process water and transferred to nitric acid bath. The temperature of the bath shall be $65^{\circ}\text{C} \pm 5^{\circ}\text{C}$, and the time in the bath shall be sufficient to give a clean bright surface on the exposed uranium.
- 520.2.3 After etching in nitric acid, the pieces shall first be thoroughly rinsed in cold process water and then in Grade A demineralized water having a resistivity of not less than .5 meg ohms/cm³. The pieces shall then be warm air dried.
- 520.2.4 After drying, the pieces shall be inspected for copper contamination, pitting or cladding defects. Pieces shall be rejected if pitting more than 0.003 inch deep, or any other obvious defects in the clad, are visible. The etched pieces shall be free of acid stains, frosty appearance or other indications of improper processing.

Approved By:

S. M. Gile
Mgr. Coext. Prod. Engr'g-FPD

11/15/61
Date

Accepted By:

J. W. Nicholas
Mgr. Coextrusion Shop -FPD

11/27/61
Date

C. R. Blum
Mgr. Quality Control -FPD

11/27/61
Date

Endorsed By:

W. Ambrose
Supvr. Reactor Fuels -FPD

11/28/61
Date

[REDACTED]

DECLASSIFIED

REPLACES SPECIFICATION
DATED 8/10/61

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 2	COPY NO.
	DATE January 15, 1962	
	SPECIFICATION NO. CX-525.0, Revision 2	

SPECIFICATION TITLE:

END CLOSURE BRAZING

525.1 Basis

The closure method selected for the NPR process consists of brazing the caps into the recessed ends of the fuel elements, followed by facing and TIG welding over the braze line. This closure meets the Fuel Criteria which require that the closure used must have a double line of defense against water entry to the uranium. The TIG weld is considered to be the primary closure backed up by the braze which has adequate corrosion resistance and integrity to exclude water from the uranium even though the weld should be defective. The braze also has the distinct advantage of providing mechanical strength to resist compressive loadings present during charging and irradiation. Further, this closure has been found to be stable during irradiation. The braze is effected by melting the preformed braze alloy ring under vacuum and allowing the molten alloy to flow around and under the cap by capillary action.

525.2 Specifications

- 525.2.1 The pieces to be closed shall be received from the chemical facility and shall be inspected for oxidation of the uranium before assembly. Any piece which shows coloring darker than light straw color, or any piece which has been exposed to air more than one (1) hour after cleaning shall be returned to the chemical facility for re-etching of the uranium.
- 525.2.2 The caps shall be placed in the recessed ends of the fuel elements and seated by pressing or driving. Forces used shall not be great enough to damage the cladding on the opposite end of the fuel element. Assemblies in which the cap was too large and resulted in bulging of the clad so that the diameter of the clad is changed by more than 0.005 inch shall be rejected. Crimping of the clad against the cap to promote, or initiate, braze flow shall be permitted provided such crimping is completely removed during the facing operation.
- 525.2.3 Assembled elements shall be placed under vacuum as soon as possible and those not evacuated to 1×10^{-3} mm Hg within fifteen (15) minutes shall be rejected. The assembled elements shall be evacuated to a pressure of 5×10^{-4} mm Hg before the brazing cycle is started.
- 525.2.4 The total brazing cycle, power-on to power-off (or coil retraction) shall not exceed one (1) minute and thirty (30) seconds. If a power-on coil retraction technique is used to control cooling, the brazing cycle shall be considered complete at the beginning of the coil retraction. The temperature, as measured optically on the top of the cap shall not exceed 1065°C, but shall be above 1040°C for the final thirty (30) seconds of the cycle. During the final thirty seconds of the cycle, the chamber shall be pressurized with argon at five (5) PSIG minimum.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

2 of 2

COPY NO.

DATE

January 15, 1962

SPECIFICATION NO.

CX-525.0, Revision 2

SPECIFICATION TITLE:

END CLOSURE BRAZING (continued)

- 525.2.5 The coil design and positioning shall be such that upon completion of the heating cycle there shall be no visually determinable difference in temperature, as evidenced by the brightness or degree of redness, over the end one (1) inch of the piece.
- 525.2.6 The heated portion of the fuel element shall be cooled in argon atmosphere to 600°C or below before exposure to the air.
- 525.2.7 Closures shall be rejected if the braze is observed to fill only from one side so that the side which did not flow is filled by metal which has flowed under the cap.

Approved By: S. M. Jee 1-16-62
Mgr. Coext. Product Engr'g - FPD Date

Accepted By: J. W. Neuholms 1-16-62
Manager, Coextrusion Shop - FPD Date
A. H. [Signature] 1-17-62
Manager, Quality Control - FPD Date

Endorsed By: [Signature] 1-18-62
Supervisor, Reactor Fuels - IPD Date

Replaces Specification
(Revision 1) dated
October 12, 1961

[REDACTED]

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 2

COPY NO.

DATE

January 12, 1962

SPECIFICATION NO.

CX-530.0, Revision 1

SPECIFICATION TITLE:

BETA HEAT TREATMENT

530.1 Basis

It is known that irradiation stability, or resistance to growth, is enhanced if the uranium has a fine grained, completely random structure. This condition is most nearly achieved by heating the fuel elements into the beta phase and then quenching into the alpha phase. The most practical method developed to date for heating the elements into the beta phase is immersion in a molten salt bath. Quenching into the alpha phase is accomplished by immersing the fuel pieces in a low temperature molten salt bath.

530.2 Specifications

530.2.1 All heat treating and quenching shall be done vertically. The inner pieces shall be supported from the tops by bails either welded or brazed to the caps. The outers shall be supported likewise, or on "T" bars from the bottom.

530.2.2 The fuel pieces shall be heated to $732 \pm 10^\circ\text{C}$ by immersion in a molten 50/50 NaCl:KCl salt bath. The salt bath shall be maintained at a temperature of $732 \pm 10^\circ\text{C}$. The pieces shall be held within a temperature range of $732 \pm 10^\circ\text{C}$ for two (2) minutes minimum, ten (10) minutes maximum.

Approved heat treating salts are Houghton Liquid Heat 168-M or Park Chemical "Nu Sal". No others shall be used without prior Engineering approval.

530.2.3 The fuel pieces shall be quenched by immersion in a molten sodium-potassium nitrate:potassium nitrite salt bath. Temperature of the quench bath shall be maintained at $300 \pm 25^\circ\text{C}$. Transfer time from the heat treating bath to the quench bath shall be such that the pieces are at $680 \pm 5^\circ\text{C}$ immediately prior to immersion in the quench bath. The pieces shall be held in the quench bath for the same residence time required for the heat treating. Chloride contamination of the quench bath shall not exceed six (6) per cent, by weight.

The approved quench bath salt is Draw Temp 275. No others shall be used without prior Engineering approval.

530.2.4 After quenching, the inner tubes shall be cooled in air for a period not less than 6.5 minutes. The outer tube shall be cooled in air for a period not less than five (5) minutes. Further cooling shall be accomplished in $60 \pm 15^\circ\text{C}$ water, or in air.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

2 of 2

DATE

January 12, 1962

SPECIFICATION NO.

CX-530.0, Revision 1

SPECIFICATION TITLE:

BETA HEAT TREATMENT (continued)

530.2.5 Pieces not heat treated within Specifications CX-530.2.1, CX-530.2.2, CX-530.2.3 and CX-530.2.4 because of mechanical or process difficulties may be re-heat treated, provided the number of heat treats does not exceed three (3). Pieces shall not be heat treated more than three (3) times for any reason.

Approved By:

S.M. Gill
Mgr. Coext. Prod. Engr'g - FPD

2/5/62
Date

Accepted By:

J.W. Nicholas
Mgr. Coextrusion Shop - FPD

2/14/62
Date

W.B. Blaser
Mgr., Quality Control - FPD

2/15/62
Date

Endorsed By:

W. Ambrose
Supervisor, Reactor Fuels- IPD

2/16/62
Date

Replaces Page 1
of CX-530.0 Dated
August 10, 1961

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS		DOCUMENT NO. HW-69941	
		PAGE NO. 1 of 1	COPY NO.
SPECIFICATION TITLE: STRAIGHTENING		DATE August 10, 1961	
		SPECIFICATION NO. CX-535.0	
<p>535.1 <u>Basis</u></p> <p>There are two basic reasons for requiring that the finished fuel elements be straight. First, it is required that the inner tube be inserted into the outer without damage to the clad or distortion of the supporting feet. Secondly, the inner tube must be properly centered within the outer tube which in turn must be centered in the process tube. Any significant deviation from this required centering will affect the flow and heat transfer characteristics of the system.</p> <p>535.2 <u>Specifications</u></p> <p>535.2.1 All pieces shall be inspected for warp after heat treating. Those showing a double throw warp, or TIR, greater than 0.030 inch but not over .075 inch shall be straightened. Pieces with TIR warp in excess of .075 inch shall be rejected.</p> <p>535.2.2 Straightening shall be accomplished by cold pressing the pieces while supported near the ends. The pieces shall be reverse bent sufficiently to result in acceptable straightness after reheat treating.</p> <p>535.2.3 All pieces which have been so straightened, or reverse bent, shall be reheat treated as specified in Specification CX-530.0.</p> <p>535.2.4 Pieces shall not be straightened more than one (1) time.</p>			
<div style="text-align: center;">[REDACTED]</div>			

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

October 10, 1961

SPECIFICATION NO.

CX-540.0, Revision 1

SPECIFICATION TITLE:

END MACHINING

540.1 Basis

The brazing operation leaves a rough as-cast braze alloy surface on the ends of the fuel elements. Also, the cladding extends slightly beyond the cap surface so that the molten braze will be prevented from flowing down the cylindrical surfaces. It is required that the excess braze and cap be machined away leaving the proper cap thickness and overall element length. Also, it is necessary to shape the cap so that the subsequent TIG weld bead will not extend beyond the cap and will have negligible overhang.

540.2 Specifications

540.2.1 The pieces shall be faced flat to remove all surplus braze alloy and give a residual cap thickness of not less than 0.200 inch.

540.2.2 The faced end of the piece shall be normal to the axis of the tube to within 0.25 degree.

*540.2.3 The inner and outer edges of the faced pieces shall be step cut, or recessed, to facilitate welding. These recesses shall be $0.030 \pm .005$ inches deep and $.075 \pm .015$ inches wide.

Approved By:

S. M. Gill
Mgr. Coext. Prod. Engr'g-FPD

10/17/61
Date

Accepted By:

J. Wickham
Mgr. Coextrusion Shop -FPD

10/20/61
Date

Q. B. Blawie
Mgr. Quality Control -FPD

11/14/61
Date

Endorsed By:

A. W. Ambrose
Supvr. Reactor Fuels -IPD

11/15/61
Date

DECLASSIFIED

Replaces Specification
dated 8/10/61

*Revised section.

DECLASSIFIED

[REDACTED] HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 1	COPY NO.
	DATE February 20, 1962	
	SPECIFICATION NO. CX-545.0, Revision 2	
SPECIFICATION TITLE: ABRASIVE CLEANING		

545.1 Basis

The high temperature of the salt bath heat treating process results in a black, hard, very tenacious film of zirconium oxide which can only be removed by abrasive means. The most practical means found to date to accomplish this oxide removal is abrasive blasting. This may be done with either dry abrasive or with the abrasive in a water slurry. Although the film is very hard and tenacious, it is normally very thin and it is possible to remove it completely without removing significant amounts of base metal.

545.2 Specifications

545.2.1 The pieces shall be cleaned before dry blasting to remove all traces of grease or cutting oil. This may be done by vapor degreasing, or scrubbing in detergent solution.

545.2.2 The outer and inner surfaces of all pieces shall be abrasive blasted. The operating procedures shall be such as to remove all traces of oxide film with a minimum amount of metal removal.

*545.2.3 The abrasive used shall be 180 mesh or finer.

545.2.4 All pieces shall be inspected for complete oxide removal and for evidence of abrasive erosion. Pieces which show remaining oxide shall be reprocessed. Pieces which show uneven or excessive metal penetration shall be measured and rejected if such measurements indicate penetration greater than 0.005 inches.

Approved By: J. M. Gill 2/21/62
Mgr. - Coextr. Prod. Engr'g - FPD Date

Accepted By: J. W. Nicholas 2/21/62
Manager - Coextrusion Shop - FPD Date

C. H. Blaschke 2/22/62
Manager - Quality Control - FPD Date

Endorsed By: A. W. Ambrose 2/26/62
Supervisor - Reactor Fuels - IPD Date

Replaces Specification
(Revision 1) dated
November 15, 1961

*0.001" average metal removal limit deleted.

UNCLASSIFIED

550.0

CONTINUATION OF BASIS

THIS preweld etch ~~shall~~^{now} be performed in two operations to allow an inspection for residual braze material on the top surface. ~~It is not necessary that be accomplished.~~
THIS ALLOWS THE RESIDUAL BRAZE ~~may~~^{TO} BE REMOVED BY RE MACHINING PRIOR TO COMPLETION OF THE pre weld etch.

R.D. Complete 3.27.64.

UNCLASSIFIED

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

August 10, 1961

SPECIFICATION NO.

CX-550.0

SPECIFICATION TITLE:

PREWELD BRIGHT ETCH

550.1 Basis

In order to get a satisfactory weld, it is necessary that the ends of the piece be cleaned of all foreign material, such as oil, grease, or abrasive grit and that it be absolutely dry. After abrasive blasting, the pieces have a dull mat finish with some imbedded abrasive particles and most likely varying degrees of oil, grease, and other contamination. The latter is removed by washing and degreasing and a specular surface is restored by bright etching in $\text{HNO}_3\text{-HF}$. The bright etch removes any smeared metal resulting from the machining operation and makes it possible to inspect the braze layer before welding. ✕

550.2 Specifications

- 550.2.1 The pieces shall be cleaned of foreign materials such as grease, oil, fingerprints, by degreasing in trichloroethylene to give a surface which will etch uniformly. *THIS MUST BE DONE BEFORE THE BRIGHT ETCH.*
- 550.2.2 The pieces shall be etched in $\text{HNO}_3\text{-HF}$ to remove up to, but not more than, 0.001 inch ^{total} of metal. ~~The bath and/or the pieces shall be vigorously agitated.~~ *Approximately 1/2 of this amount shall be removed in the first etch and the remainder in the second etch period. Pieces shall be gently agitated during etching.*
- 550.2.3 The pieces shall be transferred from the etch bath to an aluminum nitrate stop bath with no surface drying and shall be held in this bath with agitation for at least one (1) minute.
- 550.2.4 Following the stop bath, the pieces shall be rinsed in hot process water, then in demineralized water and dried in warm air.
- 550.2.5 The cylindrical surfaces shall be inspected for complete removal of the abrasive blasted finish and shall exhibit a bright, highly specular finish. Pieces not meeting these requirements shall be reprocessed.
- 550.2.6 After drying, the pieces shall be inspected for braze layer integrity. Porous braze metal or incomplete filling of the cap-clad joint shall be cause for rejection unless such defects are not over 0.030 inch deep with clean smooth bottoms which can readily be seen and are not more than 1/8 inch long.
- 550.2.7 After drying and inspection, the pieces shall be protected from contamination by moisture, acid fumes, dust or other foreign material.

[REDACTED]

DECLASSIFIED

[REDACTED]

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

October 12, 1961

SPECIFICATION NO.

CX-555.0, Revision 1

SPECIFICATION TITLE:

END CLOSURE WELDING

555.1 Basis

The TIG weld is considered to be the primary closure since it is in contact with the process water. The braze is referred to as the "second line of defense" since it would be in contact with the process water only in those cases where the weld was defective or damaged. The TIG weld is used because it gives a sound weld without contaminating the weld with dissolved gases or impure filler metal.

555.2 Specifications

555.2.1 The weld shall be effected using the Tungsten-Inert Gas (TIG) process. Argon shall be used as the inert shielding gas.

* 555.2.2 Welding conditions shall be used which result in a bright, smooth weld with weld projection beyond the cap and radial weld overhang minimized as much as practical. At least 0.010 inch of the clad surface shall be melted but molten metal shall not be permitted to extend down the cladding more than 0.180 inch, measured from the top of the cap surface. Sufficient heat must be used to melt the top edge of the step cut in all cases. The ID of the inner piece shall pass a 0.420 inch probe after welding.

555.2.3 Any welds which "blow out" or show other abnormalities, shall be rejected and no attempt shall be made to repair such welds by re-welding or making a second welding pass.

555.2.4 All welds shall be visually inspected with optical aids as required to insure that those with defects such as porosity, cracks, craters, etc., are rejected.

*Section revised.

Approved By: Sam Gill
Mgr. Coext. Product Engr'g-FPD

10/17/61
Date

Accepted By: J. W. Anderson
Mgr. Coextrusion Shop -FPD

10/20/61
Date

O. J. Blawie
Mgr. Quality Control -FPD

11/8/61
Date

Endorsed By: L. W. Ambrose
Supvr. Reactor Fuels -IPD

11/15/61
Date

Replaces Specification
dated 8/10/61

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 1

DATE

February 19, 1962

SPECIFICATION NO.

CX-560.0, Revision 1

SPECIFICATION TITLE:

FUEL ELEMENT IDENTIFICATION

560.1 Basis

It is necessary that each fuel element, both outer and inner sections, be numbered or otherwise marked so that its identity can be retained throughout the manufacturing process and also through irradiation. This identification will make it possible to correlate manufacturing history with irradiation behavior.

*560.2 Specifications

560.2.1 Each fuel element shall be identified such that the following information can be obtained from each piece at any time during manufacture or after irradiation.

- a) Extrusion number,
- b) Position in extrusion,
- c) Direction of extrusion, and
- d) Orientation with respect to die.

Failure to meet identification requirement (a) shall be cause for rejection. Failure to meet identification requirements (b), (c), and (d) shall not be cause for rejection.

560.2.2 Temporary identification of each fuel piece shall be made with a Vibratool on the front end. Such marking shall be made circumferentially on the OD cladding as near the fuel end as practical, but the location shall be such that the end machining does not destroy the identification. The depth of the Vibratool marking shall not exceed the marred surface limits.

The permanent marking shall be on the flat portion of the end cap. The size of figures used shall be such that they do not disturb the weld bead quality in any way. The marking may be done prior to welding but if so, care must be taken to insure that welding does not obliterate the numbers.

Approved By: S. M. Gell
Mgr., Coex. Product Engr'g - FPD

2/21/62
Date

Accepted By: J. W. Nicholas
Manager - Coextrusion Shop - FPD

2/21/62
Date

C. H. Blaschke
Manager - Quality Control - FPD

2/22/62
Date

Endorsed by: A. W. Ambrose
Supervisor, Reactor Fuels - IPD

2/26/62
Date

*Changes rejection requirements.

Replaces Specification
dated August 10, 1961.

DECLASSIFIED

DECLASSIFIED

████████████████████
HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

DATE

August 10, 1961

SPECIFICATION NO.

CX-565.0

SPECIFICATION TITLE:

SUPPORT AND LOCKING DEVICE WELDING

565.1 Basis

The zircaloy process tubes for the NPR have been designed and fabricated without ribs. This was done because of the difficulties involved in making ribbed tubing and also to provide flexibility for future changes in fuel element diameter. Consequently, it is necessary that some type of supports be placed on the fuel elements to center them in the process tubes. Further, it has been deemed necessary to fasten the inner piece to the outer to prevent relative motion of the two during charging or discharging. Appropriate supports and locking devices are spot welded to the clad cylindrical surface of the fuel elements.

565.2 Specifications

- 565.2.1 The number, location, and height of the supports shall be as listed in Specification CX-660.0.
- 565.2.2 The welding conditions shall be such that the resistance weld produced will not affect the bond between the clad and the uranium nor shall the uranium properties below the weld be changed.
- 565.2.3 The welding conditions shall be such that the resistance welds produced shall have strengths of not less than 500 pounds in shear per weld.
- 565.2.4 After welding, the supports and locking devices shall be gauged for position and height. They may be adjusted as required to give the proper height or conformance to support circle requirements as specified in Specification CX-660.0.
- 565.2.5 Sufficient destructive testing shall be performed to assure that the procedures used are producing the product as required by this specification.
- 565.2.6 Pieces shall be rejected if there is excessive flash indicating that the welding conditions were out of control.

<div style="background-color: black; width: 100px; height: 15px; margin: 0 auto;"></div> <p>HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS</p>		DOCUMENT NO. HW-69941	
SPECIFICATION TITLE: FINAL BRIGHT ETCH		PAGE NO. 1 of 2	COPY NO.
		DATE November 14, 1961	
		SPECIFICATION NO. CX-570.0, Revision 1	

570.1 Basis

It is absolutely essential that the zircaloy surface be clean, smooth and free of any and all contaminants before it is autoclaved in order that a black, lustrous oxide film will result. Such an oxide film is indicative of good corrosion resistance and provides a protective finish on the zircaloy. This final bright etching procedure is very critical, especially when the wide braze closure is used. Particular care must be used to insure that all fluorides are removed from the surface to prevent white oxide from forming during autoclaving. Vigorous agitation during the etch has been found to be effective in preventing fluoride buildup on the weld beads.

570.2 Specifications

- 570.2.1 Prior to bright etching, all fuel pieces shall be cleaned of surface contamination, such as fingerprints, markings, dust and oil by tri-chloroethylene degreasing and/or hot Alconox solution washing as required to give a surface which will etch uniformly.
- 570.2.2 The cleaned pieces shall be etched in an HNO_3 solution to remove between 0.0005 inch and 0.001 inch of metal per surface. During etching, the piece ~~shall be agitated~~ shall be agitated such that the solution velocity relative to the piece being etched shall not be less than 100 ft/minute along, or parallel to the axis of the piece. The pieces shall be supported so that flow through the inside of the piece shall not be hindered.
- 570.2.3 After etching, the pieces shall be transferred to an aluminum nitrate stop bath. Transfer time and conditions shall be such that surface drying can not take place. The pieces shall remain in this bath at least one (1) minute with agitation.
- 570.2.4 The pieces shall be transferred from the stop bath to a hot process rinse without surface drying. They shall be rinsed for at least two (2) minutes with vigorous agitation and then spray rinsed for one (1) minute with care being taken to insure that all inner surfaces are rinsed thoroughly.
- 570.2.5 Finally, the pieces shall be rinsed in Grade A demineralized water which shall have a resistivity of at least 500,000 ohms per cubic cm.
- *570.2.6 After final rinsing, the surfaces shall be clean with no visible sign of stain or contamination of any kind. They shall be free of pitting and shall have a highly specular appearance. The welds shall not be pitted by contact with the baskets or supporting devices and shall not be frosty or grey in appearance.

*Section revised.

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HW-69941

PAGE NO. COPY NO.
2 of 2

SPECIFICATION TITLE:

FINAL BRIGHT ETCH (continued)

DATE

November 14, 1961

SPECIFICATION NO.

CX-570.0, Revision 1

570.2.7 After etching, the pieces may be stored in Grade A demineralized water whose resistivity shall be at least 500,000 ohms/cubic cm, or may be stored dry provided they are protected from further contamination of any and all kinds.

Approved By:

S. M. Gill
Mgr. Coext. Proc. Engr'g - FPD

11/15/61
Date

Accepted By:

J. W. Nicholas
Mgr. Coextrusion Shop FPD

11/27/61
Date

O. B. Blaser
Mgr. Quality Control FPD

11/27/61
Date

Endorsed By:

A. W. Ambrose
Supervisor, Reactor Fuels-IPD

11/28/61
Date

Replaces Specification,
Page 1, dated 8/12/61

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 2

COPY NO.

SPECIFICATION TITLE:

AUTOCLAVE TESTING

DATE

August 12, 1961

SPECIFICATION NO.

CX-575.0

575.1 Basis

The autoclave test serves three purposes, (1) it is a proof test of the integrity of the cladding; although it cannot be guaranteed that all cladding defects will become apparent during autoclaving it is believed that the chances of failure due to cladding defects during irradiation will be substantially reduced if the fuel elements have been so tested, (2) autoclaving provides an indication of the corrosion resistance of the finished fuel element. Even the relatively short test possible should indicate gross corrosion weaknesses which might result in failure, and (3) the black, glossy film produced by the autoclave tests effectively passivates the surface and renders it less likely to be affected by surface contamination. This makes handling much simpler during the charging operation.

575.2 Specifications

575.2.1 The standard autoclave test shall meet the following conditions:

Medium	-	Superheated Steam
Temperature	-	400 $\pm$ 20°C
Pressure	-	1500 $\pm$ 100 PSIG
Time	-	Seventy-two (72) hours minimum at specified temperature and pressure

575.2.2 At least two (2) per cent of total production shall be subjected to the following alternate autoclave cycle which is a more rigorous evaluation of the corrosion properties of the cladding.

Medium	-	Deionized Water	<i>MIN Temp 345°C</i>
Temperature	-	360 $\pm$ 15°C +10, -15 °C	<i>MIN press 2850 PSI</i>
Pressure	-	2850 $\pm$ 100 PSI	<i>MAX Temp 360°C</i>
Time	-	Fourteen (14) days (336 Hours)	<i>MIN press 2850</i>

Fuel elements processed according to this cycle, in lieu of the standard cycle shall be considered as acceptable pieces. ~~Records shall be kept on the number of pieces which fail to pass both this test and the standard test. Such records will serve as the basis for possible revision of the standard test.~~

The material subjected to the alternate test shall be chosen, if possible, to evaluate the corrosion characteristics of different lots, or groups, of material which may vary significantly because of different manufacturing history, different component suppliers, etc.

575.2.3 In both the standard and alternate tests, the autoclaves shall be instrumented and controlled to assure that the steam, or water, as the case may be, in contact with all surfaces of all elements being tested is within the temperature limits specified in Sections 575.2.1 and 575.2.2.

[REDACTED]

DECLASSIFIED

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

2 of 2

COPY NO.

DATE

August 12, 1961

SPECIFICATION NO.

CX-575.0 (cont.)

SPECIFICATION TITLE:

AUTOCLAVE TESTING (continued)

- 575.2.4 After autoclaving, the zircaloy surfaces shall exhibit a black, glossy appearance with no indication of acid staining, white oxide or other sub-standard conditions. The weld beads may show a dull black or dark grey rather than the glossy black normal for autoclaved zircaloy. However, the weld beads shall not show light grey or white oxide. Visual standards of acceptable and unacceptable autoclaved weld beads shall be prepared and used. Any evidence of rust or other significant foreign material on the autoclaved surfaces shall be cause for rejection. All elements in an autoclave charge shall be rejected if a rupture occurs in any element.
- 575.2.5 The autoclaves and accessories used to carry out the specified tests shall be constructed, maintained and operated such that the fuel element surfaces shall be protected from contamination of all kinds. Particular care shall be taken in cases of rupture or other suspected uranium contamination. The autoclaves and accessories shall be cleaned and rinsed until all traces of uranium are removed. *to reduce uranium contamination on fuel surfaces by deposit above background*
- 575.2.6 To conserve autoclave capacity, it shall be permissible to assemble inner and outer pieces. Insertion and removal shall be done with the pieces in the vertical position to minimize scratching. *to reduce uranium contamination by deposit above background*

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 1

DATE

January 9, 1962

SPECIFICATION NO.

CX-585.0, Revision 1

SPECIFICATION TITLE:

FINAL INSPECTION AND ASSEMBLY

585.1 Basis

After autoclaving, the pieces must be given a final inspection, largely for marred surfaces or other handling damage. The iron shoes will be crimped on the outer supports and the inner pieces inserted into the outers and permanently locked into place. This is the last opportunity to inspect all but the outer surface.

585.2 Specifications

585.2.1 All surfaces shall be inspected visually, with optical aids as required, to insure that the autoclave film is intact; that the pieces have not been marred, scratched or dented in any way that would compromise their integrity; and that they are ready for final assembly. Pieces which are marred, scratched or dented beyond the limits of Specification CX-660.213 shall be rejected.

585.2.2 The iron shoes shall be crimped to the outer supports so as to insure that they will not come off during charging or discharging. The support circle shall be rechecked after application of the shoes.

585.2.3 The inner piece shall be inserted into the outer and locked into final position. Assembly shall be done with the pieces held vertically. Further, assembly shall be accomplished such that objectionable galling does not occur on the inside surface of the outer tube. It shall not be permissible to use undue force to effect mating of the locking device and its companion support.

The inner tube shall not protrude beyond the outer tube on either end.

Approved By:

S. M. Gile
Mgr., Coextr. Prod. Engr'g - FPD

1-16-62
Date

Accepted By:

J. W. Nicholas
Manager, Coextrusion Shop - FPD
C. B. Smith
Manager, Quality Control - FPD

1-16-62
Date

1-17-62
Date

Endorsed By:

J. W. Ambrose
Supervisor, Reactor Fuels - IPD

1-18-62
Date

DECLASSIFIED

Replaces Specification
dated August 11, 1961

DECLASSIFIED

<div data-bbox="668 131 1081 196" style="text-align: center;">[REDACTED]</div> <div data-bbox="618 209 1132 269" style="text-align: center;">HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS</div>	DOCUMENT NO.	
	HW-69941	
	PAGE NO.	COPY NO.
	1 of 1	
SPECIFICATION TITLE: STORAGE AND SHIPMENT	DATE	
	August 11, 1961	
	SPECIFICATION NO. CX-590.0	

590.1 Basis

Inasmuch as the first elements manufactured will not be reactor charged for some months, it will be necessary to store them in such manner as to prevent both physical damage and surface contamination as well. The relatively great weight of the assembled elements requires special care during handling, storage and shipment.

590.2 Specifications

- 590.2.1 The fuel elements shall be stored and shipped in covered containers which adequately provide for keeping them clean and dry.
- 590.2.2 The pallets or boxes used for storage and shipment shall be constructed in such a way that the piece is held firmly in position against soft bearing supports, such as heavy felt, plastic or similar material. The material used for such bearing supports, however, shall not be one which will decompose in time and stain or contaminate the surface of the zircaloy.
- 590.2.3 Immediately prior to the loading of each pallet with fuel elements, it shall be thoroughly cleaned and inspected to assure that the fuel element will not be damaged.
- 590.2.4 The inner fuel piece shall be supported rigidly with respect to the outer piece to prevent any possible damage to the inner tube supports during storage, moving or shipment.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 2

DATE

January 15, 1962

SPECIFICATION NO.

CX-615.0, Revision 1

SPECIFICATION TITLE:

EXTRUSION SAMPLE EVALUATION

615.1 Basis

It is required that the extruded tubes be evaluated to assure that they are of adequate quality to result in acceptable fuel elements. Certain phases of the extrusion evaluation can be done only by destructive tests on samples cut from the extrusion for this purpose. Other tests, which can be done by nondestructive techniques, are performed throughout the fabrication process at the most convenient time.

615.2 Specifications

615.2.1 Bond Strength

The quality, or strength of the bond shall be evaluated on all extrusions by use of the peel test as described in HW-64553, except that for purposes of this specification the definitions of the classifications shall be revised as indicated at the end of this specification. At least three (3) bond strength samples shall be cut from each extrusion; one from each end and one from the center. The end samples shall be taken outside (or closer to the ends of the extrusion) of any pieces to be processed as fuel elements. If the two end samples have ratings of "Good", then the center sample need not be evaluated. If either of the end samples has a "Fair" rating, then the center sample shall be evaluated. If the center sample is found to be "Good" or "Fair", the extrusion shall be judged to be acceptable. If it is found to be "Poor", the tube shall be considered "suspect" and shall be further evaluated to guarantee that no material is used which has a "Poor" bond. If either of the end samples has a "Poor" rating, at least five (5) additional inches shall be cropped and discarded before proceeding as outlined above.

615.2.2 Interface Roughness

Inasmuch as both the eddy current clad thickness test and the auto-radiograph test are quite insensitive to interface roughness, it is required that at least a qualitative test or inspection be made to assure that improperly heat treated uranium has not resulted in objectionable interface roughness. This shall be done by examining the exposed cladding after chemical milling or by examining the exposed cladding after etching the uranium from bond samples.

615.2.3 Surface Roughness or Rippling

The surface of the finished fuel pieces shall not exhibit roughness or rippling in excess of 0.002 inch above or below the mean surface.

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;">[REDACTED]</div> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS	DOCUMENT NO. HW-69941	
	PAGE NO. 2 of 2	COPY NO.
	DATE January 15, 1962	
	SPECIFICATION NO. CX-615.0, Revision 1	

SPECIFICATION TITLE:
EXTRUSION SAMPLE EVALUATION (continued)

BOND STRENGTH DEFINITIONS:

The bond strengths shall be determined on rings cut from the extrusion at least 0.250 inches wide. At least three outer and three inner tests shall be made per outer sample and at least two each per inner tube sample. The following definitions shall apply:

- a) "Good" - To qualify as a "Good" bond strength test, there must be no visible separation of the cladding and the uranium at the bond line. Varying grain structure may result in varying degrees of roughness or different angles of fracture.
- b) "Fair" - A "Fair" bond may have some separation at the bond line but such separation shall not exceed 3/32 inch at any point across the sample.
- c) "Poor" - Any instance in which there is a separation which exceeds 3/32 inch at any point across the sample shall be considered "Poor".

In all cases, the poorest rating in any one sample shall determine the rating for that sample.

Approved By: S.M. Jell 1-16-62
Mgr., Coextruded Product Engr'g-FPD Date

Accepted By: J.W. Nicholas 1-16-62
Manager - Coextrusion Shop -FPD Date

C.Y. Blasewitz 1/17/62
Manager - Quality Control -FPD Date

Endorsed By: J.W. Ambrose 1-18-62
Supervisor - Reactor Fuels -IPD Date

Replaces Specification
dated August 12, 1961.

[REDACTED]
HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

COPY NO.

1 of 1
DATE

September 18, 1961
SPECIFICATION NO.

CX-620.0 - Rev. 1

SPECIFICATION TITLE:

CLAD-CORE BOND TEST

620.1 Basis

It is required that the uranium to zircaloy bond be tested for completeness and uniformity. Incomplete bonding will likely result in hot-spots during irradiation.

620.2 Specifications

*620.2.1 The entire uranium-zircaloy bond shall be ultrasonically tested for completeness. A 25 megacycle, lithium sulfate crystal shall be used as the source. The rotation and translation of the piece and crystal shall be such that 100 per cent of the surface specified shall be scanned.

620.2.2 Fuel element pieces which give a positive unbond indication shall be rejected.

620.2.3 The internal and external bond test shall be standardized on a known unbond standard. The standard shall be checked before and after any test period and every hour during use. Any indicated abnormalities shall be reason for rechecking of the standards. In case of malfunction or lack of sensitivity found during standardization, all material processed since the most recent satisfactory check shall be rerun.

*Deletion of items in parentheses

Approved by: S. M. Gee
Mgr. Coext. Prod. Engr. - FPD

Accepted by: J. W. Nicholas
Mgr. Coextrusion Shop - FPD

Accepted by: C. G. Blawie
Mgr. Quality Control - FPD

Endorsed by: H. W. Ambrose
Supvr. Reactor Fuels - IPD

Replaces Specification
dated 8/11/61

DECLASSIFIED

UNCLASSIFIED

<div style="border: 1px solid black; width: 150px; height: 15px; margin: 0 auto;"></div> <p>HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS</p>		DOCUMENT NO. HW-69941	
SPECIFICATION TITLE: CLAD THICKNESS TEST		PAGE NO. 1 of 1	COPY NO.
		DATE February 22, 1962	
		SPECIFICATION NO. CX-625.0, Revision 1	

625.1 Basis

A minimum clad thickness is required to assure protection of the uranium from the reactor coolant and to provide the clad strength needed for satisfactory irradiation of the coextruded fuel elements.

625.2 Specifications

625.2.1 To determine clad thickness, the entire zircaloy clad surface (except for approximately 1/4 inch at each end) shall be eddy current tested using optimum methods and techniques. A continuous plot of the test data shall be made. The rotation and translation of the piece and the test head shall be such that 100 per cent of the surface shall be checked.

*625.2.2 The following limits shall be used as the basis for rejection of pieces:

<u>Location</u>	<u>Minimum</u>	<u>Maximum Circumferential Variation</u>
Outer Tube - OD	0.020"	0.008"
Outer Tube - ID	0.020"	0.008"
Inner Tube - OD	0.035"	0.010"
Inner Tube - ID	0.020"	0.008"

A piece shall be rejected if the eddy current test clearly indicates, in light of known eddy current test capabilities, that the piece is outside the above limits. (Refer to Specification CX-655.0, Revision 1).

625.2.3 The internal and external testers shall be standardized with a fuel section with known clad thickness before and after each test period and every hour during use. Any time the tester has drifted more than 0.002", it shall be recalibrated and all material run since the last satisfactory calibration shall be rechecked.

Approved By: S.M. Gice 2/28/62
Mgr., Coext. Product Engr'g - FPD Date

Accepted By: J.W. Nicholas 2/28/62
Manager - Coextrusion Shop - FPD Date

[Signature] 3/1/62
Manager, Quality Control - FPD Date

Endorsed By: H.W. Ambrose 3/2/62
Supervisor - Reactor Fuels - IPD Date

*The requirement that the eddy current and autoradiograph test results be averaged was deleted.

Replaces Specification
dated August 12, 1961.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.

1 of 1

COPY NO.

SPECIFICATION TITLE:

CAP-CORE BOND TEST

DATE

August 12, 1961

SPECIFICATION NO.

CX-635.0

635.1 Basis

It is required that the cap be bonded to the uranium core to provide additional corrosion resistance and mechanical strength. The integrity of this bond can be verified by ultrasonic testing methods.

635.2 Specifications

- 635.2.1 The bond between the cap and the uranium core shall be tested for completeness using a ten megacycle lithium sulfate crystal. The transducer shall be fixed with respect to the fuel element and the width of the crystal shall be such that the entire cap width can be inspected with one pass.
- 635.2.2 Any closure which gives a cap-core unbond signal equivalent to, or greater than, that produced by a 1/3-inch diameter unbond standard shall be rejected.
- 635.2.3 The tester shall be calibrated against an unbond standard before and after each test period and at least once each hour during use. If the standard does not give an unbond signal, the tester shall be adjusted or repaired, and all material processed since the last calibration shall be re-run.

[REDACTED]

DECLASSIFIED

DECLASSIFIED

<div style="text-align: center;"> HANFORD ATOMIC PRODUCTS OPERATION COEXTRUSION PROCESS SPECIFICATIONS </div>	DOCUMENT NO. HW-69941	
	PAGE NO. 1 of 1	COPY NO.
	DATE October 12, 1961 SPECIFICATION NO. CX-640.0, Revision 2	
SPECIFICATION TITLE: CAP-CLAD BOND TEST		

640.1 Basis

The brazing process must bond the cap to the clad as well as to the core. It is required that a test be made to insure that bonding between the cap and the clad is complete and that there are no significant voids in the braze layer between the cap and the clad.

640.2 Specifications*

640.2.1 The bond and braze layer between cap and the clad shall be inspected for completeness and absence of voids using a fifteen megacycle ultrasonic pulse echo technique. A lithium sulfate crystal shall be used as the source.

640.2.2 The instrument shall be calibrated against a known unbond standard before and after each test run and at least once each hour during use. If the standard does not produce an unbond signal, the instrument shall be adjusted or repaired and all material tested since the last calibration check shall be rechecked.

*Deletion of item 640.2.2 from Specifications as dated 9/16/61.

Approved By:	<u>S. M. Gill</u>	<u>10/17/61</u>
	Mgr. Coext. Product Engr'g-FPD	Date
Accepted By:	<u>J. W. Nicholas</u>	<u>10/20/61</u>
	Mgr. Coextrusion Shop -FPD	Date
	<u>C. B. Blawie</u>	<u>11/8/61</u>
	Mgr. Quality Control -FPD	Date
Endorsed By:	<u>H. W. Ambrose</u>	<u>11/15/61</u>
	Supvr. Reactor Fuels -IPD	Date

Replaces Specification
dated 9/18/61

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

HW-69941

PAGE NO.
1 of 1

COPY NO.

SPECIFICATION TITLE:

AUTORADIOGRAPHIC CLAD THICKNESS TEST

DATE

February 26, 1962

SPECIFICATION NO.

CX-655.0, Revision 1

655.1 Basis

Since the eddy current test is known to be somewhat insensitive to small defects, and since it also overlooks some narrow longitudinal streaks, it is advisable to autoradiograph all material. It may not prove necessary to read all films completely for absolute clad thickness determination, but all films must be scanned for defect detection.

655.2 Specifications

- 655.2.1 Both surfaces of all pieces shall be autoradiographed by the best known techniques to evaluate clad thickness and detect unusual flaws or small areas of substandard cladding.
- 655.2.2 A piece shall be rejected if the results of the eddy current test and the autoradiograph test indicate that the piece is outside the limits of Specification CX-625.2.2.
- 655.2.3 A piece shall be rejected if the autoradiograph test indicates small spots or areas not detectable with the eddy current tester are outside the limits of Specification CX-625.2.2.
- 655.2.4 Any evidence of "pinholes" or other such defects shall be cause for rejection. In some cases, however, repeat exposures may be desirable because of faulty films or other abnormalities.
- *655.2.5 In some cases, not covered by Specifications CX-655.2.2, CX-655.2.3 or CX-655.2.4, the autoradiograph test and the eddy current test results may be contradictory. In such cases the pieces shall be rejected if the test, which most reliably measures the clad thickness at the clad defect, indicates the clad is outside the limits of Specification CX-625.2.2.

Approved By:

S. M. Gier
Mgr. - Coextrusion Product Engr'g - FPD

2/28/62
Date

Accepted By:

J. W. Nicholas
Manager - Coextrusion Shop - FPD

2/28/62
Date

C. H. Blawie
Manager - Quality Control - FPD

3/1/62
Date

Endorsed By:

L. W. Ambrose
Supervisor - Reactor Fuels - IPD

3/2/62
Date

*The requirement that the eddy current and autoradiograph test results be averaged was deleted.

DECLASSIFIED

Replaces Specification
dated August 12, 1961

DECLASSIFIED

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.

~~HW-69941~~

PAGE NO.
1 of 3

COPY NO.

DATE

February 21, 1962

SPECIFICATION NO.

CX-660.0, Revision 2

SPECIFICATION TITLE:

REFERENCE TABLE OF CRITICAL DIMENSIONS

660.1 Basis

A table of critical dimensions is provided for quick reference both during the process steps and during final inspection.

660.2 Specified Critical Dimensions

660.2.1 Final Lengths

a) Outer Tubes	(E)	23.140" - 23.260"
		17.340" - 17.460"
		11.540" - 11.660"
	(N)	19.840" - 19.960"
b) Inner Tubes	(E)	23.080" - 23.200"
		17.280" - 17.400"
		11.480" - 11.600"
	(N)	19.780" - 19.900"

* 660.2.2 Final Diameters (Excluding Closures)

a) Outer Tubes	OD	2.396" - 2.416"
	ID	1.754" - 1.774"
b) Inner Tubes	OD	1.242" - 1.256"
	ID	0.431" - 0.445"
c) Reworked Outer Tubes Only	OD	2.391" - 2.416"
	ID	1.754" - 1.779"
d) Reworked Inner Tubes Only	OD	1.237" - 1.256"
	ID	0.431" - 0.450"

* 660.2.3 Maximum Wall Thickness Variation (Excluding Closures)

a) Outer Tubes	0.030"
b) Inner Tubes	0.030"

660.2.4 Warp

a) Outer Tubes	0.030" - Maximum TIR
b) Inner Tubes	0.030" - Maximum TIR

* Per I.P.D. analysis.

[REDACTED]

HANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS

DOCUMENT NO.
HW-69941

PAGE NO.
2 of 3

COPY NO.

SPECIFICATION TITLE:

DATE

February 21, 1962

SPECIFICATION NO.
CX-660.0, Revision 2

REFERENCE TABLE OF CRITICAL DIMENSIONS (continued)

660.2.5 Support Location - Longitudinal

a) Outer Tube	(Support Center)	2.910" - 3.090 from end
b) Inner Tube		
End Supports	(Support Center)	2.910" - 3.090" from end
c) Inner Tube		
Center Supports	(Omit 11.53" tubes)	±0.200"
d) Locking Device		Meet requirements of
Specification CX-585.2.3.

660.2.6 Support Spacing - Circumferential

a) Outer Supports	88° - 92°
b) Inner Tube	118° - 122°

660.2.7 Support Circle Diameter

a) Outer Tube	(With Shoes)	2.675" - 2.685"
b) Inner Tube Ends	←	1.796" Maximum
1.774" Minimum
c) Inner Tube Center		1.720" Minimum
1.796" Maximum

660.2.8 Eccentricity of Support Circle 0.005" Maximum

660.2.9 Cap Thickness

a) Outer Tubes	0.200" Minimum
b) Inner Tubes	0.200" Minimum

660.2.10 Final Minimum Clad Thickness

a) Outer Tube-Outer Clad	0.019"
b) Outer Tube-Inner Clad	0.019"
c) Inner Tube-Outer Clad	0.034"
d) Inner Tube-Inner Clad	0.019"

DECLASSIFIED

DECLASSIFIED

MANFORD ATOMIC PRODUCTS OPERATION
COEXTRUSION PROCESS SPECIFICATIONS 3073

DOCUMENT NO. HW-69941	
PAGE NO. 1-6-3	COPY NO.
DATE February 21, 1962	
SPECIFICATION NO. CX-660.0, Revision 2	

ICATION TITLE:

ERENCE TABLE OF CRITICAL DIMENSIONS (continued)

*660.2.11 Maximum Circumferential Clad Variation

a) Outer Tube-Outer Clad	0.008"
b) Outer Tube-Inner Clad	0.008"
c) Inner Tube-Outer Clad	0.010"
d) Inner Tube-Inner Clad	0.008"

660.2.12 Supports & Locking Device Thickness

a) Outer Supports	0.035" Minimum
b) Inner Supports	0.030" Minimum
c) Locking Device	0.040" Minimum

660.2.13 Braze Recess Depth

a) Outer Tubes	0.300" - 0.320"
b) Inner Tubes	0.300" - 0.320"

660.2.14 Marred Surfaces

a) .025" Cladding	0.002" Maximum
b) .040" Cladding	0.003" Maximum
c) On Closure (Excluding flat face)	0.005" Maximum
d) On Closure Face	0.010" Maximum

ed By: Sm Gile 2/21/62
Mgr. Coextr. Product Engr'g - FPD Date

ed By: J W Ambrose 2/21/62
Manager - Coextrusion Shop - FPD Date

W J Blawie 2/22/62
Manager - Quality Control - FPD Date

ed By: J W Ambrose 2/26/62
Supervisor, Reactor Fuels - IPD Date

P.D. analysis.

Replaces Specification
(Pages 1 and 2) dated
January 12, 1962.(Rev. 1)

DATE

FILMED

7 / 1 / 94

END