**DOE/MC/25003-3045
(DE92001121)**

**ENHANCED DURABILITY OF HIGH-TEMPERATURE DESULFURIZATION
SORBENTS FOR MOVING-BED APPLICATIONS BASE PROGRAM:
DEVELOPMENT AND TESTING OF ZINC FERRITE SORBENTS**

Topical Report

**By
R. E. Ayala**

August 1991

Work Performed Under Contract No. AC21-88MC25003

**For
U.S. Department of Energy
Morgantown Energy Technology Center
Morgantown, West Virginia**

**By
General Electric Company
Schenectady, New York**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, FTS 626-8401.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

DOE/MC/25003--3045

DE92 001121

**Enhanced Durability of High-Temperature Desulfurization
Sorbents for Moving-Bed Applications
Base Program: Development and Testing of
Zinc Ferrite Sorbents**

Topical Report

R.E. Ayala

Work Performed Under Contract No.: DE-AC21-88MC25003

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
General Electric Company
GE Corporate Research and Development
P.O. Box 8
Schenectady, New York 12301**

August 1991

ABSTRACT

The integrated gasification combined-cycle (IGCC) power system using high-temperature desulfurization is one of the most promising advanced technologies for the production of electric power from coal because the high-temperature desulfurization step eliminates efficiency losses associated with coal gas scrubbing and requirements for expensive heat recovery equipment. High-temperature desulfurization research in the U.S. over the past several years has concentrated on mixed-metal oxide sorbents, particularly zinc ferrite, which can remove hydrogen sulfide and other reduced sulfur species from raw coal gas to less than 10 parts per million by volume (ppmv) and can be regenerated for multicycle operation.

The objective of this research was to identify and implement compositions and fabrication methods that enhance the long-term chemical reactivity and mechanical strength of zinc ferrite sorbents for the GE moving-bed, high-temperature desulfurization of coal-derived gases. In the GE moving-bed process, the pelletized sorbent slowly moves between the absorber and regenerator vessels; thus a mechanically strong and chemically active sorbent is necessary.

Twenty zinc ferrite sorbent formulations were prepared as ellipsoidal pellets using a novel rounding process. Four fabrication variables were studied: binder type (e.g., bentonite, calcium aluminate, calcium sulfate), binder concentration (up to 17%), calcination temperature (1450-1750 °F), and iron oxide type (pigment and catalyst grades). Mechanical strength was assessed by measuring pellet crush strength and sorbent attrition resistance at 70 °F and 1000 °F. Fresh sorbent crush strength was measured up to 28 lb/pellet and fresh sorbent attrition resistance was measured up to 97.5% in ellipsoidal pellets having acceptable chemical reactivity. This is a 9.8% increase from 88.8% attrition resistance of previous cylindrical extrudates (i.e., baseline formulation). The corresponding mechanical strength for sorbents exposed to 10 cycles of absorption and regeneration were measured up to 26.1 lb/pellet crush strength and 91.1% attrition resistance, both in formulation L-3769M.

Chemical reactivity was measured by thermogravimetric analysis (TGA); bench-scale, packed-bed reactor testing; and various bulk and surface chemical analysis techniques such as XRD, XRF, SEM/EDX, and SEM/EMA. Average sorbent bed utilization at breakthrough ranged from 6.4 to 37.2% of the theoretical value for zinc ferrite based on pellet sulfur analyses. The performance of the five zinc ferrite formulations tested over 10 cycles of H₂S absorption and regeneration in a bench-scale reactor system indicates that mechanically and chemically durable sorbents for moving-bed applications can be prepared by rounding sorbents into ellipsoidal pellets, rather than cylindrical extrudates. Chemical reactivity and mechanical strength were generally found to be inversely related. Sorbents having bentonite-only binder exhibited higher reactivity but were mechanically weak after cyclic use while calcium-containing binders provided higher mechanical strength at the expense of lower reactivity. Hence, a compromise was necessary to produce a formulation that was both chemically and mechanically superior. Formulation L-3769M, containing 10% calcium sulfate/3% bentonite binder, was found to exhibit the best overall performance.

ACKNOWLEDGMENTS

This project was sponsored by the U.S. Department of Energy (DOE)/Morgantown Energy Technology Center (METC), under Contract No. DE-AC21-88MC25003. The author would like to acknowledge the technical guidance and discussions with Mr. Suresh C. Jain, METC Contracting Officer Representative (COR). The technical discussions and contributions to this project are acknowledged from Dr. Eli Gal, GE Environmental Systems, Inc. (GEESI), and Drs. Santosh K. Gangwal and Raghubir Gupta, Research Triangle Institute (RTI), in the areas of sorbent mechanical testing and single-pellet TGA measurements and characterization, respectively. The technical contribution of United Catalysts, Inc., (UCI) as a sorbent supplier is also acknowledged. Special thanks to S. Gene Kimura and Anthony H. Furman, GE Corporate Research and Development, for their valuable input and advice. R. Ayala would like to express his appreciation to Josephine Sykes, Tim Chuck, David Germain and the rest of our technical group at GE Corporate Research and Development (GE-CRD) for the excellent work in the laboratory.

TABLE OF CONTENTS

Section	Page
ABSTRACT	iii
ACKNOWLEDGMENTS	v
LIST OF TABLES	ix
LIST OF FIGURES	xi
EXECUTIVE SUMMARY	1
1 INTRODUCTION	5
1.1 Contract Objectives	5
1.2 Background Information	5
1.2.1 High-Temperature Desulfurization Systems	5
1.2.2 Sorbent Development	7
1.2.3 Zinc Ferrite Chemistry	8
1.3 Base Program Description	9
1.4 Sorbent Screening Criteria	10
2 FRESH SORBENT PREPARATION AND CHARACTERIZATION	13
2.1 Selection of Sorbent Manufacturing Parameters	13
2.2 Experimental Procedures	14
2.2.1 Sorbent Preparation	14
2.2.2 TGA Chemical Reactivity	14
2.2.3 Sorbent Chemical Analyses	15
2.2.4 Sorbent Physical Morphology	16
2.2.5 Mechanical Strength	16
2.3 Fresh Sorbent Characterization Results	17
2.3.1 Application of Criterion 1	17
2.2.2 TGA Chemical Reactivity	20
2.2.3 Mechanical Strength	23
2.2.4 Application of Criterion 2	24
3 PROVISION OF BENCH-SCALE UNIT	26
3.1 Gas Handling System	26
3.2 Reactor System	27
3.3 Gas Analysis System	28
4 BENCH-SCALE TESTING	29
4.1 Bench-Scale Experimental Procedure	29
4.2 Bench-Scale Results	29

TABLE OF CONTENTS (Cont'd)

Section	Page
5 BENCH-SCALE ANALYSIS	37
5.1 Single-Pellet TGA Chemical Reactivity	37
5.2 Pellet Physical Morphology	37
5.3 Sorbent Mechanical Strength	40
5.4 Pellet Chemical Composition	43
5.5 Application of Criterion 3 (Superior Formulation)	50
6 CONCLUSIONS AND RECOMMENDATIONS	54
REFERENCES	57

LIST OF TABLES

Table	Page
1 Gas Compositions (Volume Percent) for TGA Tests	15
2 Fresh Zinc Ferrite Formulations	18
3 UCI Fresh Zinc Ferrite Characterization	19
4 TGA Reactivity for Additional Zinc Ferrite Formulations	22
5 Porosimetry Data from TGA Zinc Ferrite Samples	23
6 Bench-Scale Unit Test Conditions	27
7 Bench-Scale Reactor Test Conditions	29
8 Pore Characterization of Bench-Scale Reactor Sorbents	40
9 Chemical Analysis of Bench-Scale Sorbents (10 th Absorption)	44
10 Chemical Analysis of Bench-Scale Sorbents (10 th Oxidative Regeneration)	47
11 SEM/EMA Zn:Fe Ratio as Function of Pellet Radial Location	48
12 XRF Average Pellet Composition of 10 th Regeneration	50
13 Summary Data for Criterion 3	53

LIST OF ILLUSTRATIONS

Figure	Page
1 Schematic diagram of the simplified Integrated Gasification Combined-Cycle (IGCC) system	6
2 GE moving-bed system within the Process Evaluation Facility	7
3 Experimental criteria for sorbent screening	11
4 High-temperature attrition tester	17
5 TGA chemical reactivity for various zinc ferrite formulations	20
6 Comparison of TGA fractional conversion with minimum requirements for the moving-bed system (0.5 fractional conversion in 2 hr)	21
7 Comparison of first and second sulfidation TGA reactivity for L-3404 and L-3407	22
8 Attrition resistance of zinc ferrite formulations at 70 °F and 1000 °F	24
9 Attrition resistance of T-2465M at 70 °F for various test durations with and without fines removal	25
10 Schematic diagram of the bench-scale reactor system	26
11 Schematic diagram of the reactor vessel	28
12 H ₂ S breakthrough curves for L-3404, T-2465M, and L-3407 zinc ferrite sorbents	31
13 H ₂ S breakthrough curves for L-3769M and L-3770M zinc ferrite formulations	32
14 Reactor bed center temperatures for regeneration of T-2465M	34
15 Reactor outlet SO ₂ concentration during oxidative regeneration of L-3770M	34
16 SO ₂ and H ₂ S reactor outlet concentrations during reductive regeneration of L-3769M	35
17 SO ₂ and H ₂ S reactor outlet concentrations during reductive regeneration of L-3770M	36
18 TGA chemical reactivity of L-3404, T-2465M, and L-3407 sorbents extracted from the bench-scale reactor system after the 10 th oxidative regeneration	38
19 TGA chemical reactivity of L-3769M and L-3770M sorbents extracted from the bench-scale reactor system after the 10 th oxidative regeneration	39
20 Attrition resistance and crush strength of five sorbents extracted from the bench-scale reactor system after the 10 th oxidative regeneration	41

LIST OF ILLUSTRATIONS (Cont'd)

Figure		Page
21	Attrition resistance and crush strength of five sorbents extracted from the bench-scale reactor system after the 10 th absorption	42
22	SEM/EMA of L-3404 and L-3407 sorbent samples (gas inlet) extracted from the bench-scale reactor system after the 10 th oxidative regeneration	46
23	SEM/EDX Fe, Zn, and S maps of L-3404 sorbent sample (gas inlet) extracted from the bench-scale reactor system after the 10 th absorption	49
24	SEM/EDX Fe, Zn, and S maps of L-3407 sorbent sample (gas inlet) extracted from the bench-scale reactor system after the 10 th absorption	51
25	Comparison of overall performance of zinc ferrite sorbents under Criterion 3	53

EXECUTIVE SUMMARY

BACKGROUND

The integrated gasification combined-cycle (IGCC) power system using high-temperature coal gas cleanup is one of the most promising advanced technologies for the production of electric power from coal in an environmentally acceptable manner. In conventional cleanup systems, costly heat exchangers are necessary to cool down the gases for cleaning. Unlike these conventional low-temperature systems, high-temperature coal gas cleanup systems can be operated at 1000 °F or higher and 20 atmospheres of pressure, which are conditions compatible with the gasifier and turbine components in the IGCC system. The result is a more efficient overall system.

The General Electric Company (GE) is developing a moving-bed high-temperature desulfurization system in which zinc ferrite is currently being used as a desulfurization sorbent. In addition to zinc ferrite, zinc titanates and other novel mixed-metal oxides are also being considered as sorbents, particularly for cases of highly reducing coal gases where the use of iron-containing sorbents may be limited by the formation of iron carbides and other iron species that result in sorbent degradation. Any sorbent selected should not undergo undesired reactions, such as sulfate formation during regeneration, and the process should be able to control the heat released during regeneration. The GE moving-bed system is believed to minimize some of the limitations of zinc ferrite and provide an opportunity for demonstration of the feasibility of using various mixed-metal oxides for high-temperature desulfurization of coal gas in a commercial system.

OBJECTIVE

The objective of this contract is to identify and test fabrication methods and sorbent chemical compositions that enhance the long-term chemical reactivity and mechanical strength of zinc ferrite and other novel sorbents for moving-bed, high-temperature desulfurization of coal-derived gases. Zinc ferrite sorbents were studied under the Base program of this contract while novel sorbents, including zinc titanates, will be studied under the remaining optional programs. This topical report summarizes the work performed under the Base program only.

ACCOMPLISHMENTS

- Built and operated a bench-scale reactor system for testing of up to three zinc ferrite sorbent formulations simultaneously over multiple cycles of absorption and regeneration at conditions simulating those encountered in the GE moving-bed system.
- Evaluated twenty zinc ferrite formulations for chemical reactivity and mechanical properties, prepared using a rounding technique, and selected five promising formulations for testing in the bench-scale reactor.
- Identified the most promising zinc ferrite formulation, containing 10% calcium sulfate and 3% bentonite binder, which maintained excellent chemical reactivity and mechanical performance over long-term testing in the bench-scale reactor.

RESULTS AND CONCLUSIONS

The use of zinc ferrite as a sorbent for high-temperature, moving-bed systems was evaluated at the bench-scale level. From the analysis of the results, the following conclusions can be made:

1. The use of the rounding technique for the fabrication of rounded ellipsoidal zinc ferrite pellets significantly increases the mechanical strength of the resulting pellets over that of cylindrical extrudates having the same chemical composition. Attrition resistance was increased from 88.8% for the baseline cylindrical extrudate up to 97.5% for rounded ellipsoidal pellets.
2. Binder chemical composition has a major effect on the mechanical strength and chemical reactivity of the resulting sorbent formulations by affecting the pore structure (specific pore volume and median pore diameter). After extended 10-cycle testing in the bench-scale reactor system, the binder performance can be summarized as follows:
 - The combination of calcium sulfate (10% wt/wt) and bentonite (2% wt/wt) gave the best overall performance in terms of high mechanical strength (both attrition resistance and crush strength) and acceptable chemical reactivity (single-pellet TGA and bench-scale testing) of all formulations tested in the bench-scale reactor system.
 - Bentonite alone (2-3%) imparted the porosity necessary for high chemical reactivity, but does not inhibit losses in attrition resistance and crush strength.
 - Calcium aluminate (12%)/bentonite (3% by weight) introduced added mechanical strength (both crush strength and attrition resistance) at the expense of gradual lower chemical reactivity through the extended reactor testing. This behavior was a result of the formation of calcium-sulfur compounds that added strength but decreased the specific pore volume of the pellet.
3. The performance of the five zinc ferrite formulations tested over 10 cycles of H₂S absorption and regeneration in a bench-scale reactor system indicates that chemically and mechanically durable sorbents suitable for moving-bed systems can be fabricated as ellipsoidal pellets. However, chemical reactivity and mechanical strength were found to be inversely related because denser, less porous formulations were found to be stronger and, generally, less reactive. A trade-off between these two properties is necessary in order to produce a formulation that is both chemically and mechanically acceptable. L-3769M, containing 10% calcium sulfate and 3% bentonite was found to be the formulation having the best overall balance of the two properties.
4. Sorbent reactivity in the bench-scale reactor was determined by comparing the calculated the dimensionless time at the 200 ppm H₂S breakthrough, which is related to the theoretical sulfur capacity of the sorbent and eliminates differences in binder content of the sorbents. Dimensionless times are generally defined as the ratio of real time to the time required to flow a theoretical amount of H₂S through the sorbent bed that would result in 100% sulfidation of the sorbent. The dimensionless time at the 200 ppmv breakthrough for each of the five sorbents tested in the bench-scale reactor ranged from 0.05 to 0.30 (or 5-30% of theoretical bed capacity) and followed the trend:

$$L-3407 < L-3770M < L-3769M < T-2465M < L-3404$$

This trend was explained by differences in specific pore volumes of the sorbents before and after the testing. Chemical analyses for total sulfur on sulfided pellets extracted from the

reactor bed translated into actual average sorbent utilizations up to 37% (50.8% at the gas inlet location; 22.5% at the gas outlet location) of the theoretical values for zinc ferrite at the 200 ppmv breakthrough. The measured bed utilizations correlated very well with predicted dimensionless times.

5. Measured reactor pre-breakthrough H_2S effluent concentrations, 15 ppmv or less, are satisfactory for the use of any of the laboratory-tested five sorbent formulations in commercial high-temperature desulfurization systems. These pre-breakthrough concentrations translate into approximately 99.9% sulfur removal from the simulated coal gas.
6. Reductive regeneration during bench-scale testing releases short bursts of SO_2 and H_2S up to 4000 ppmv for the first two minutes. Even though most of the sulfate formed during oxidative regeneration at 1000 °F was decomposed by the last step of oxidative regeneration (1400 °F under air for 2 hours), reductive regeneration might always be necessary. Using the GE moving-bed system, the reductive regeneration gases containing SO_2 does not represent an emission problem since they are returned to the gasifier, to the absorber, or sent to the SO_2 treatment process.
7. Sorbent formulations that maintained comparable specific pore volume, SPV, as fresh and as cycled materials, such as L-3404, also maintained the chemical reactivity through the 10 cycles of testing. Those that experienced a significant decrease in SPV, such as L-3407, did not maintain the same reactivity. Satisfactory pore volumes for zinc ferrite sorbents were in the range 0.20 to 0.30 cc/g. Smaller SPVs became more susceptible to pore plugging, incomplete regenerability, and loss of reactivity.
8. Amounts of residual carbon after bench-scale testing were always less than 0.20%. The low values are probably due to the high-steam simulated gas composition used and do not represent a problem for system operation.
9. Elemental analysis of regenerated pellets from the bench-scale reactor by SEM/EDX and SEM/EMA showed homogeneous microscopic distribution of zinc in L-3407, containing calcium aluminate binder, but segregation into microscopic clusters in L-3404, containing bentonite binder only. Distribution of Fe, Zn, and S across the pellet diameter revealed migration of zinc from the outside to the center of the pellet in both cases, more so in L-3407, presumably because of zinc vaporization followed by capillary condensation in inner smaller pores of the pellet. Hence, zinc evaporation was not a problem under the conditions tested but zinc migration may be a cause for the decrease in reactivity of L-3407.
10. Residual sulfur, excluding binder sulfur, in the regenerated samples was usually less than 0.5% by weight, which represents a small amount of the sulfur uptake during absorption, measured up to 18.8% total sulfur, or 20.0 g sulfur/100 g sorbent. Sulfate sulfur was between 16 and 65% of the residual sulfur.

RECOMMENDATIONS

- To further study the use of calcium-based binders and other cements in zinc ferrite sorbents; calcium-based binders (e.g., calcium aluminate and calcium sulfate) were found to increase the mechanical strength of the sorbent over multiple-cycle testing above bentonite and other binders. The key issue is to be able to control pore size within a narrow range in order to prevent pore plugging on sulfidation.

- To determine the long-term effect of other contaminants in the coal gas (e.g., tars, chloride, ammonia, alkali) on the desulfurization performance of zinc ferrite.
- To explore the use of additives to zinc ferrite for enhanced performance such as tar cracking, ammonia decomposition, and alkali removal. Metal oxides used in the petroleum refining industry could be used as starting candidates.
- To investigate the use of other mixed-metal oxides, such as zinc titanates, for desulfurization of highly-reducing gases where iron oxide has limited use. In addition, to determine the degree of metal migration or segregation as a result of temperature and/or concentration gradients within the sorbent pellets.
- To adopt a standard attrition test that incorporates weighting factors for pellet size distribution instead of the current ASTM D4058-81 where only oversize (+20 mesh) and undersize (-20 mesh) are compared.

SECTION 1

INTRODUCTION

1.1 CONTRACT OBJECTIVES

The objective of this contract was to identify and test fabrication methods and sorbent chemical compositions that enhance the long-term chemical reactivity and mechanical strength of zinc ferrite and other novel sorbents for moving-bed, high-temperature desulfurization of coal-derived gases. Zinc ferrite sorbents were studied under the Base program of this contract while novel sorbents, including zinc titanates, will be studied under the remaining optional programs. This topical report summarizes the work performed under the Base program only.

Desired properties to be enhanced for moving-bed sorbent materials are: (1) high chemical reactivity (sulfur absorption rate and total sulfur capacity), (2) high mechanical strength (pellet crush strength and attrition resistance), and (3) suitable pellet morphology (e.g., pellet size, shape, surface area, and average specific pore volume). In addition, it is desired to maintain the sorbent properties over extended cyclic use in moving-bed systems.

1.2 BACKGROUND INFORMATION

The integrated gasification combined-cycle (IGCC) power system using high-temperature coal gas cleanup is one of the most promising advanced technologies for the production of electric power from coal in an environmentally compatible way. Shown in Figure 1 is a schematic of the IGCC system. Coal is first converted to gas in a gasifier. Then, various pollutants, such as solid particles and sulfur species (e.g., H_2S and COS), are removed from the coal gas in the cleanup system. Finally, the clean coal gas is burned in a gas turbine to produce electricity. Conventional cleanup systems use energy-inefficient, low-temperature scrubbing processes where costly heat exchanger systems are necessary to cool the gas from the gasifier, handle the water condensate, and reheat the gas (Corman, 1986).

Unlike conventional cleanup systems, high-temperature coal gas cleanup systems can be operated at approximately 1000 °F and 20 atmospheres, which are conditions compatible with the gasifier and turbine components in the IGCC system. The result is a more efficient overall system. A description of high-temperature desulfurization systems is given below.

1.2.1 High-Temperature Desulfurization Systems

Several configurations of high-temperature desulfurization systems have been considered for future large-scale applications. These are the fixed-bed, the moving-bed, and the fluidized-bed systems. Two of the most developed configurations are currently the fixed-bed and the moving-bed systems.

The U.S. Department of Energy (DOE) at the Morgantown Energy Technology Center has supported fixed-bed and moving-bed systems using zinc ferrite sorbent over the past ten years. A pilot-scale fixed-bed system was tested at KRW's facilities using a single vessel although a complete design requires a minimum of two vessels (one vessel in the absorption mode while the other is in the regeneration mode) (Haldipur, 1988). Texaco also tested a fixed-bed system (Wu et al., 1989) with three parallel, fixed-bed reactors for external polishing desulfurization of a slip stream of the gasifier using

Figure 1. Schematic diagram of the simplified Integrated Gasification Combined-Cycle (IGCC) system.

zinc ferrite and zinc titanate sorbents. The bulk of desulfurization was performed in the gasifier by in-situ desulfurization with iron oxide.

The General Electric Company (GE) is currently developing a moving-bed system as an alternative to the fixed-bed system for high-temperature desulfurization. A schematic representation of the GE moving-bed system is shown in Figure 2. The coal gas from the gasifier initially goes through a high-efficiency cyclone to collect entrained particles. The gas then goes through the moving-bed absorber in a countercurrent fashion where the sulfur species (mainly H_2S and COS) are removed down to approximately 10 ppmv. The sulfided sorbent moves down slowly and leaves the bottom of the absorber vessel through a lockhopper and continues to move down by gravity to the regenerator, which is also a slowly moving bed. The sulfided sorbent is then regenerated at nearly atmospheric conditions in three stages of increasing oxygen concentrations with the evolution of SO_2 . Details of the operation of the GE moving-bed system have been discussed previously by Smith (Smith et al., 1987).

A recent technical and economic evaluation of fixed beds and moving beds was performed by DOE/METC, and concluded that the moving-bed system has technical advantages over the fixed-bed system (Koch, 1989). For instance, the fixed-bed system alternates between absorption and regeneration in each vessel that results in shifts in pressure, temperature, and oxygen content that may damage the vessel materials in the long run. Instead, the moving-bed system operates near steady state by slowly moving the sorbent. Furthermore, the moving-bed produces a regeneration off gas with a high enough SO_2 concentration (10-12%) suitable for direct production of sulfuric acid. The fixed bed requires all vessels to withstand high temperatures and high pressures with an extensive arrangement of valves and piping. Fine particles in the fixed bed are hard to remove during operation because they are not flowing; in the moving bed they are removed at the bottom of the regenerator.

Figure 2. GE moving-bed system within the Process Evaluation Facility.

A fluidized-bed system using an iron oxide sorbent is being implemented in Japan (Sugitani, 1987). However, the use of iron oxide as the sulfur sorbent limits the removal of hydrogen sulfide to levels to only 100 ppmv at best, and sorbent mechanical degradation due to attrition was measured to be significant. Currently there is a significant effort by DOE/METC and its contractors to develop a fluidized-bed desulfurization system using zinc ferrite as a sorbent to circumvent the limitations of iron oxide (Gangwal, 1990), but the level of development is behind that of fixed beds and moving beds and no thorough technical or economic evaluation has been made as in the other cases.

12.2 Sorbent Development

Development over the past several years of sorbents suitable for high-temperature desulfurization has concentrated on mixed-metal oxides, particularly zinc ferrite, which can remove hydrogen sulfide from raw coal gas to less than 10 ppmv and can be regenerated for multicycle operation (Grindley and Steinfeld, 1985; Gangwal et al., 1989a; Gangwal et al., 1989b; Ayala et al., 1990).

A major portion of the past work on zinc ferrite has been for development of sorbent extrudates suitable for fixed-bed operation (Jha et al., 1989). Recently, research has been sponsored by METC for development of zinc ferrite sorbents suitable for moving-bed and fluid-bed applications (Cook et al., 1989; Jain et al., 1990; Gangwal and Harkins, 1989).

In addition, zinc titanates and other novel mixed-metal oxides are also being considered (Flytzani-

Stephanopoulos et al., 1990; Jalan et al., 1989), particularly for cases of highly reducing coal gases (i.e., coal gases containing a large fraction of H₂ or a high CO/CO₂ ratio) where the use of iron-containing sorbents may be limited by the formation of iron carbides and sorbent decrepitation because of reduction of iron oxide. The effort under this contract on the development of novel sorbents for moving-bed applications will be presented in a future report.

1.2.3 Zinc Ferrite Chemistry

Zinc ferrite, ZnFe₂O₄, is a mixed-metal oxide having a crystalline spinel structure formed by two metal oxides: ZnO and Fe₂O₃ (Kolts et al., 1980). The chemistry of zinc ferrite during high-temperature desulfurization of coal gases involves several reactions which have been summarized recently (Ayala and Marsh, 1991).

The overall reaction describing the absorption of H₂S from coal gas is given by

Reaction 1-1 can be considered essentially irreversible since the equilibrium vapor pressure of H₂S over ZnFe₂O₄ is very low (i.e., < 10 ppmv) at process temperatures near 1000 °F. Zinc ferrite sorbent performance in high-temperature desulfurization is very sensitive to temperature and coal gas composition. For instance, in the presence of coal gases with high H₂ content or high CO/CO₂ ratio, the iron portion of zinc ferrite is reduced to FeO or Fe, which leads to the formation of iron carbide, Fe₃C (Lamoreaux et al., 1986). The formation of Fe₃C and other carbides is particularly detrimental for sulfur absorption because Fe₃C reduces the sulfur capacity of the sorbent and induces stresses due to solid density differences that result in mechanical disintegration of pellets.

The regeneration of zinc and iron sulfides by oxygen back to the original zinc ferrite structure is given by the following overall reaction:

Reaction 1-2 is highly exothermic with a heat of reaction of -1700 kJ/mol. Similarly to absorption, regeneration of zinc ferrite depends on temperature as well as gas composition. For instance, at low temperatures (i.e., below 900 °F) and under high SO₂ and O₂ concentrations, zinc and iron sulfates are formed during regeneration according to the following mechanisms (Krishnan et al., 1985).

Sulfate formation according to reactions (1-3) and (1-4) can be significant depending on gas composition at temperatures below the thermal decomposition temperature of $\text{Fe}_2(\text{SO}_4)_3$ (896 °F) and ZnSO_4 (1112 °F). Its deleterious effect during cyclic absorption and regeneration results because the sulfate is reduced during absorption following regeneration releasing SO_2 into the clean coal gas according to

The above undesired reactions can be circumvented by selecting process conditions that minimize the sulfate formation, for instance, regeneration above the thermal decomposition point of iron and zinc sulfates, and the use of low initial oxygen concentrations. The GE moving-bed system is believed to minimize some of the limitations of zinc ferrite and provide an opportunity of demonstration of the feasibility for using mixed-metal oxides for high-temperature desulfurization of coal gas. Results of modeling of a moving-bed absorber/regenerator system using zinc ferrite have been published in the past (Ayala and Kim, 1989).

1.3 BASE PROGRAM DESCRIPTION

The goal of the Base Program was to identify and test sorbent fabrication methods and sorbent chemical compositions that enhance the long-term chemical reactivity and mechanical strength of zinc ferrite sorbent formulations for moving-bed, high-temperature desulfurization of coal-derived gases. The work was divided into six tasks with the following objectives:

Task 1 - Experimental Test Plan

Objective - To prepare the experimental test plan for DOE/METC review and approval. The plan included identification, development, and demonstration of methods for enhancing the chemical reactivity and mechanical strength of the COTR-designated zinc ferrite formulation for moving-bed desulfurization reactor applications. The test plan included: sorbent preparation methods, chemical characterization methods for fresh and cycled formulations, description of criteria for selection of enhanced formulations, details of bench-scale, reactor unit, analytical equipment, and test matrix of proposed tests.

Task 2 - Sorbent Preparation

Objective - To prepare and characterize various zinc ferrite formulations in forms suitable for moving-bed desulfurization of hot coal gases.

Task 3 - Provision of Bench-Scale Unit

Objective - To provide a bench-scale test unit per the approved test plan. The bench-scale was provided in a manner to facilitate transportation to other test locations, if required.

Task 4 - Bench-Scale Testing

Objective - Testing of 4 formulations of the zinc ferrite sorbent through at least 10 cycles of operation per the approved test plan.

Task 5 – Bench-Scale Test Analysis

Objective - To analyze cycled sorbent formulations from the bench-scale unit and determine the amount of deterioration in mechanical as well as chemical properties that occurred during cyclic testing.

Task 6 – Topical Report

Objective - To provide a report containing detailed analysis of sorbent characteristics before and after long-term cyclic testing.

The program structure allocated the work to each of the following program participants: GE Corporate Research and Development (GE-CRD, prime contractor), GE Environmental Services (GEES, subcontractor), Research Triangle Institute (RTI, subcontractor), and United Catalysts, Inc. (sorbent supplier).

1.4 SORBENT SCREENING CRITERIA

In order for a sorbent to be considered for moving-bed applications it must withstand continual transport between absorber and regenerator vessels without losing pellet mechanical integrity nor experiencing losses in chemical reactivity due to repetitive cycling. Hence, the sorbent has to meet certain minimum requirements for:

- Pellet morphology (e.g., pore volume, pore diameter, size, shape)
- Mechanical strength (crush strength and attrition resistance) of fresh sorbent
- Chemical reactivity (sulfur absorption, or sulfidation rate) of fresh sorbent
- Sulfur-loading capacity of fresh sorbent
- Mechanical Strength (crush strength and attrition resistance) of cycled sorbent
- Chemical reactivity (sulfur absorption rate) of cycled sorbent
- Sulfur-loading capacity of cycled sorbent

The specifications of minimum requirements have been grouped into three criteria, applied successively at three decision points in the program (Figure 3). Specifications of the minimum requirements for pellet morphology and mechanical strength for fresh formulations constitute Criterion 1 (to be applied under Task 2 – Sorbent Preparation). Only those formulations that meet Criterion 1 would be selected and further analyzed to determine whether they meet the minimum requirements for fresh sorbent chemical reactivity and sulfur capacity under Criterion 2 (to be applied under Task 2 also). Only those formulations that meet Criterion 2 would be selected and tested in the bench-scale reactor unit.

Three criteria were used as guidelines to assess sorbent performance and identify superior formulations for moving-bed systems:

Figure 3. Experimental criteria for sorbent screening.

Criterion 1:

- Higher attrition resistance than that for the Baseline zinc ferrite formulation (2% bentonite binder). Attrition resistance is defined in Section 2.2.5.
- Specific pore volume in the range 0.2 to 0.3 cm³/g.
- Average pore diameter greater than 1000 Å.

Criterion 2:

- Single-pellet chemical reactivity requirements:
 - TGA fractional conversion greater than 0.5 (i.e., 50% conversion) in 2 hours at standard conditions (1022 °F, 1 atm., 3% H₂S).
 - TGA sulfur loading capacity greater than 70% of theoretical for zinc ferrite.
- Mechanical strength requirements:
 - Crush strength greater than 20 lb/pellet for the fresh material.
 - Attrition resistance greater than 94%, according to ASTM procedure D4058-81, at ambient and high temperature.

Criterion 3:

- Weighted compromise between chemical reactivity and mechanical strength (defined in the analysis of bench-scale test results).

Criterion 1 is applied to fresh formulations obtained from the sorbent supplier, United Catalysts, Inc. (UCI), to select those suitable for single pellet chemical reactivity and mechanical strength measurements. Criterion 2 is applied to those formulations meeting Criterion 1 in order to select those for bench-scale reactor testing. Criterion 3 would be applied to those formulations meeting Criterion 2 to select an overall superior formulation.

Although there are no final numbers as to what level of mechanical strength and/or reactivity constitute minimum requirements for the successful use over long times of a sorbent formulation in a full scale moving-bed hot gas cleanup system, the values selected for the sorbent screening criteria in this program reflect what is considered a significant enhancement of sorbent properties to give confidence of satisfactory long-term performance of the sorbent.

Selection of the Baseline Sorbent Formulation

T-2465 zinc ferrite, manufactured by United Catalysts, Inc., (UCI) was selected by DOE/METC as the baseline formulation for this program. All new zinc ferrite formulations were compared against this baseline formulation to screen potentially superior sorbents. T-2465 is a cylindrical pellet with a length of 1/4 in. and a diameter of 3/16 in. having UCI catalyst-grade iron oxide and 2% inorganic bentonite binder. The sorbent was calcined at 1550 °F for 2 hours.

SECTION 2

FRESH SORBENT PREPARATION AND CHARACTERIZATION

2.1 SELECTION OF SORBENT MANUFACTURING PARAMETERS

A sorbent to be considered suitable for moving-bed desulfurization systems has to possess satisfactory chemical reactivity and mechanical strength through continuous transport between absorber and regenerator vessels. Eight important parameters in the manufacturing process generally identified as enhancing durability of desulfurization sorbent formulations were considered:

1. Pellet Size
2. Pellet Shape
3. Binder Type
4. Binder Content
5. Calcination Temperature
6. Calcination Time
7. Chemical Composition
8. Iron Oxide Type

Because an attempt to study all eight parameters as variables would have resulted in an excessively large test matrix for this program, only those that were expected to have a major impact on strength and reactivity were considered as test matrix variables. Four parameters were selected as the test matrix variables and four were left as fixed parameters.

The selected four test matrix variables are:

- Binder type
- Binder content
- Calcination temperature
- Iron oxide type

The fixed parameters are:

Pellet shape:	ellipsoidal
Pellet size:	1/4 in. (nominal)
Calcination time:	2 hours
Chemical composition:	1:1 ZnO:Fe ₂ O ₃

2.2 EXPERIMENTAL PROCEDURES

2.2.1 Sorbent Preparation

Zinc ferrite, ZnFe_2O_4 , was prepared by first producing equimolar mixtures of zinc oxide, ZnO and ferric oxide, Fe_2O_3 , powder in the presence of a suitable binder. The powder mixture was then wet extruded and rounded into ellipsoidal pellets using a continuous rounding machine. Finally, the pellets were calcined at temperatures above 1450 °F. More details of the fabrication procedure are proprietary to UCI, the sorbent vendor, and hence not available.

After rounding, ellipsoidal pellets had an average 0.64 cm major axis and aspect ratio between 1.1 and 1.3. An average pellet mass of 350 mg $\pm$ 10% was found to be a good representation of all formulations. Fabrication parameters selected for study were:

- Binder type: bentonite, calcium aluminate, Portland cement, titanium dioxide, calcium sulfate, organic burnout filler.
- Binder content: total up to 17% by weight
- Calcination temperature: 1450, 1550 and 1750 °F
- Iron oxide type: catalyst and pigment grade.

In addition to inorganic binders, some formulations were also prepared by adding 5-10% wt. organic burnout filler which decomposed upon calcination and left a more open porous structure in the pellet. A porous structure increases chemical reactivity by reducing pore diffusivity of the gaseous reactants during desulfurization. Results of the sorbent preparation procedure are presented in Section 2.3 Fresh Sorbent Characterization Results.

2.2.2 TGA Chemical Reactivity

Chemical reactivity of the sorbent was determined by measuring single-pellet sorbent sulfur capacity (defined as grams of sulfur absorbed per 100 g of fresh sorbent) and regenerability in a thermogravimetric analyzer (TGA). Zinc ferrite reaction chemistry which can be used to relate weight changes to sulfur capacity has been described elsewhere (Woods et al., 1989). The TGA procedure is described in the following paragraphs.

The TGA is based on a Cahn Instrument Model 1000 balance having a sample capacity of up to 100 g, and capable of measuring weight changes with an accuracy of $\pm 1 \mu\text{g}$. The TGA can monitor weight changes of a single pellet suspended from a hangdown wire attached to the electrobalance mechanism. Additional pellets (up to 4) are placed downstream on a stainless steel screen supported on the thermowell so that a total of 5 pellets are exposed to the same gaseous environment and enough samples are available for further chemical analysis. The single pellet is positioned at the center of the middle zone, and the additional pellets are positioned approximately 1/2 in. downstream. Pellet weight changes are used as an indication of the extent of chemical reaction during sulfidation and regeneration.

The gas compositions used for reduction, sulfidation, and regeneration in the Base program are shown in Table 1. The test procedure consisted of a 30-minute reduction at 1022 °F (550 °C) in clean reducing gas prior to each sulfidation. Sulfidation is then conducted at 1022 °F (550 °C) with 3% H_2S

for both the 1/2-cycle (i.e., sulfidation) runs and the 1-1/2-cycle (i.e., sulfidation-regeneration-sulfidation) runs. This concentration enabled us to complete a TGA run in one day or less. The tests are conducted for a minimum of 3 hours or until no weight change occurs.

After full sulfidation, oxidative regeneration is carried out at 1250 °F with 4% O₂ in N₂. At this point, the run is interrupted if necessary to remove one pellet from the screen for characterization of surface area and pore volume. The remaining pellets were then subjected to a second reduction and sulfidation prior to termination of the run. All of the 1-1/2-cycle screening tests were conducted at 1 atm. pressure. All of the sample pellets tested were selected to be of nearly equivalent size so that the sorbents are compared on an equivalent basis.

Table 1. Gas Compositions (Volume Percent)
for TGA Tests

	Reducing Gas	Sulfiding Gas	Regeneration Gas
H ₂	15.0	15.0	-
CO	8.0	8.0	-
CO ₂	11.0	11.0	-
H ₂ S	-	3.0	-
H ₂ O	30.0	30.0	-
N ₂	36.0	33.0	96.0
O ₂	-	-	4.0

2.2.3 Sorbent Chemical Analyses

Although most of the chemical analyses described in this section were conducted on pellets extracted from the bench-scale reactor, the description of the analytical techniques is included in here so as to keep all experimental procedures together as part of Section 2.2, Experimental Procedures.

The crystalline phase composition of selected formulations subjected to single-pellet TGA tests was determined using x-ray diffraction (XRD). The instrument used for analysis is a Rigaku θ/θ automated diffractometer with a 43-position sample changer. The lower detection limit for most constituents is approximately 1 vol.%.

Microstructure and qualitative elemental distribution of zinc, iron, and sulfur across the pellet cross section (i.e., elemental maps) were determined by scanning electron microscopy (SEM) coupled to energy dispersive x-ray analysis (EDX), respectively. Semi-quantitative analysis for zinc, iron, and sulfur at various locations within a pellet was performed using electron microprobe analysis (EMA). SEM/EDX and SEM/EMA allowed us to determine the extent of chemical inhomogeneities in the cross section of a pellet due to exposure to simulated coal gases at high temperature. Quantitative average elemental analysis of whole pellets from selected formulations was determined by inductively-couple plasma (ICP) spectroscopy, x-ray fluorescence, or proton-induced x-ray emission (PIXE) spectroscopy for higher sensitivity. Quantitative average concentration of selected compounds was determined by x-ray fluorescence (XRF) spectrometry. Average content of total carbon and total sulfur in single pellets was determined by total carbon and total sulfur analyses by Commercial Testing and Engineering, Co. (South Holland, Illinois) using a LECO analyzer.

2.2.4 Sorbent physical morphology

Pore volume distributions and the median pore diameter (i.e., diameter at 50% intrusion) of selected fresh and used sorbents from the TGA were measured using a Micromeritics mercury porosimeter (Wood et al., 1989).

2.2.5 Mechanical Strength

The mechanical strength of sorbents was determined by measurements of crush strength and attrition resistance. Crush strength (i.e., deadweight load) was measured by subjecting single pellets to an increasing load until breakage occurred, and the measured force was averaged over a minimum of 20 pellets. Attrition tests were performed in a rotating cylinder, and the weight loss of sorbent on attrition was measured according to a modified ASTM D4058-81 method at ambient temperature and at 1000 °F. In this study, attrition resistance is defined as 100% minus the loss on attrition. Loss on attrition is determined in the above ASTM D4058-81 method by calculating the difference in measured weight of the sample retained in a No. 20 (850 μ m) ASTM sieve before and after rotating the cylinder at 60 rpm for 30 minutes. Attrition rate is defined as the rate of change of loss on attrition with respect to time.

Attrition tests were performed according to a modified ASTM procedure D4058-81, "Attrition and Abrasion of Catalysts and Catalyst Carriers." The apparatus was built under this contract according to the recommended ASTM specifications for measurements at ambient temperature and modified to accommodate testing at elevated temperatures (e.g., 1000 °F). Testing of attrition resistance at high temperature was desired in order to establish a correlation, if any, between attrition at ambient temperature (i.e., ASTM test) and attrition at actual operating temperature during desulfurization.

Figure 4 shows the schematic configuration of the attrition tester. The rotating cylinder is built of 10 in. I.D. 304 stainless steel pipe, 6 in. in length, with a baffle inside according to the specifications of ASTM test D4058-81, "Attrition and Abrasion of Catalysts and Catalyst Carriers." Since the operation of the tester requires heating of the cylinder to temperatures near 1000 °F, the rubber seal between the lid and the cylinder itself was deleted from the ASTM design and the cover machined with a lip providing a good match to the cylinder and using Allen screws. Heat is provided by a furnace (7.5 amps, 900 watts at 120 V. AC) rated for 1500 °F maximum. The temperature is controlled by a single-point proportional Omega controller connected to the furnace through a solid-state relay. Rotation of the cylinder is accomplished through a 3/8 in. stainless steel shaft attached to a 3/4 HP skid-mounted motor and supported by two pillow blocks. Rotational speed of the cylinder is adjusted by a variable-voltage controller attached to the motor.

For the standard ASTM procedure D4058-81, a sample of about 100 grams is rotated for 30 minutes at a rate of 60 rpm, after which the fine particles (-20 ASTM sieve) are separated and their weight percentage is determined and compared with the minimum acceptable requirements. For high-temperature attrition tests, the rotating cylinder is heated by the ceramic furnace. The furnace temperature is controlled to any desired set point (e.g., 1000 °F) and allowed to achieve a steady temperature before starting rotation. After the sample has been rotated for 30 minutes at 60 rpm, the furnace is turned off. The sample is then cooled down and the percentage of fine particles is determined to arrive at the attrition resistance. Tests were also conducted for longer than 30 minutes in duration to be able to extrapolate sorbent performance during long-term operation.

Figure 4. High-temperature attrition tester.

2.3 FRESH SORBENT CHARACTERIZATION RESULTS

2.3.1 Application of Criterion 1

Twenty formulations were tested under the Base Program and shown in Table 2, most of them being fabricated specifically under this program and some procured from other sources for evaluation. Each formulation represents a unique combination of fabrication parameters and procedures.

As seen in Table 2, L-3406 is the only formulation prepared with pigment-grade iron oxide (Mobay Bayferrox 645T) while the rest contained UCI catalyst-grade iron oxide. Pigment-grade iron oxide contains higher levels of impurities. L-3770M was produced as a densified formulation by rounding it first, then crushing, and finally rounding again with the goal of adding strength to the final ellipsoidal pellet. T-2465M was originally prepared as a 20,000-lb batch under another DOE-sponsored program (Contract DE-AC21-87MC23170) for testing in the moving-bed, pilot-scale facility at GE-CRD. T-2465M was prepared using UCI's pilot-scale equipment instead of laboratory equipment (hence, the "L" designation for the laboratory formulations). L-2814 is a cylindrical pellet previously prepared by UCI for GE that exhibited unusually high attrition resistance. The purpose of considering L-2814 in this program was to fully test it for chemical reactivity and regenerability.

Results of the sorbent characterization, as performed by UCI, are presented in Table 3. The following observations can be made:

- The rounding procedure to make ellipsoidal pellets increases the mechanical strength over conventional extrusion into cylindrical pellets. Of those formulations containing 2% bentonite binder, ellipsoidal T-2465M and L-3404 exhibited higher attrition resistance than cylindrical T-2465 (Baseline formulation).
- All formulations met the desired values for specific pore volume, SPV, and median pore diameter, MPD, for fresh formulations.

Table 2. Fresh Zinc Ferrite Formulations*

Formulation	Calcination Temp. (°F)	Pellet Shape	Binder Content (%)
T-2465	1550	Cylindrical	2% Bentonite
T-2465M	1550	Ellipsoidal	2% Bentonite
L-3404	1550	Ellipsoidal	2% Bentonite
	1750	Ellipsoidal	2% Bentonite
L-3405	1550	Ellipsoidal	5% Bentonite
	1750	Ellipsoidal	5% Bentonite
L-3406**	1550	Ellipsoidal	2% Bentonite
	1750	Ellipsoidal	2% Bentonite
L-3407	1550	Ellipsoidal	3% Bentonite
			12% Ca Aluminate
	1750	Ellipsoidal	3% Bentonite
			12% Ca Aluminate
L-3407A	1550	Ellipsoidal	3% Bentonite
			12% Ca Aluminate
			5% Org. Burnout
	1750	Ellipsoidal	3% Bentonite
			12% Ca Aluminate
			5% Org. Burnout
L-3408	1550	Ellipsoidal	3% Bentonite
			12% Portland Cement
	1750	Ellipsoidal	3% Bentonite
			12% Portland Cement
L-3409	1550	Ellipsoidal	3% Bentonite
			15% Ca Aluminate
			2% Anatase TiO ₂
	1750	Ellipsoidal	3% Bentonite
			15% Ca Aluminate
			2% Anatase TiO ₂
L-3467A	1750	Ellipsoidal	2% Bentonite
			15% Ca Aluminate
L-3467B	1750	Ellipsoidal	2% Bentonite
			15% Ca Aluminate
L-3769M	1450	Ellipsoidal	2% Bentonite
			10% Ca Sulfate
L-3770M	1450	Ellipsoidal	2% Bentonite
L-2814	1550	Cylindrical	2% Bentonite
			18% Ca Aluminate

* As provided by the manufacturer United Catalyst, Inc.

** Contains Mobay Bayferrox 645T pigment-grade iron oxide.
All others use UCI catalyst-grade.

Table 3. UCI Fresh Zinc Ferrite Characterization

Formulation	Calcination Temp. (°F)	Attrition Resist.(%)	Surface Area (m ² /g)	SPV ^a cc/g	MPD ^b (Å)
T-2465*	1550	88.8			2430
T-2465M	1550	95.4	4.6	0.20	1958
L-3404	1550	91.0	3.8	0.25	2185
	1750	90.0	3.4	0.25	3040
L-3405	1550	94.0	5.0	0.25	2060
	1750	94.5	4.4	0.20	2330
L-3406	1550	96.0	5.2	0.19	2190
	1750	95.5	5.1	0.24	2330
L-3407	1550	95.0	7.0	0.24	1095
	1750	96.0	4.9	0.31	3180
L-3407A	1550	93.0	8.7	0.30	2185
	1750	95.0	4.2	0.25	3180
L-3408	1550	88.0	3.5	0.25	3180
	1750	91.0	3.3	0.31	3040
L-3409	1550	92.0	9.2	0.23	1165
	1750	92.0	6.4	0.19	1630
L-3467A	1750	88.0	4.9	0.20	2500
L-3467B	1750	90.0	4.2	0.32	3180
L-3769M	1450	95.5	4.2	0.24	2190
L-3770M	1450	97.5	4.6	0.22	2190
L-2814	1550	99.2		0.21	719

* Baseline formulation (cylindrical extrudate)

^aSpecific Pore Volume^bMedian Pore Diameter

- L-3406, prepared with pigment-grade iron oxide, has comparable mechanical properties to L-3404 and T-2465M, prepared from catalyst-grade iron oxide, so the differences in iron oxide grades do not affect the mechanical properties of the fresh sorbents.
- Calcium aluminate (12%) and bentonite (2-3%) binders added to several formulations introduces added attrition resistance compared to those containing anatase TiO₂ (2%), and Portland cement (12%)
- Attrition resistance and crush strength are weak functions of calcination temperature. A slight increase in attrition resistance crush strength were observed for formulations calcined at 1750 °F instead of 1550 °F. Crush strength variation with temperature were within the reproducibility of the measurement.
- Surface area is inversely proportional to calcination temperature but did not have a correlation with mechanical strength. Hence, surface area will not be consired further as an indicator of pellet mechanical strength.

Because all formulations essentially met Criterion 1 requirements for specific pore volume and median pore diameter, formulations selected for further testing were those meeting the fresh attrition resistance test (namely, having an attrition resistance greater than the Baseline). Hence, formulations

L-3404, L-3406, L-3407, L-3409, L-3769M, L-3770M, T-2465M, and L-2814 were selected as the top candidates for TGA chemical reactivity testing.

2.3.2 TGA chemical reactivity

Selected samples from UCI were subjected to 1/2-cycle sulfidation runs and 1 1/2-cycle sulfidation-regeneration-sulfidation runs as described in Section 2.2.2 TGA Chemical Reactivity.

Results of TGA chemical reactivity for various formulations are presented in Figure 5. Weight fraction is defined as the pellet weight at a given time divided by the initial pellet weight after heat-up and prior to the initial reduction. Comparison of the formulations tested shows that the L-3404 sorbent reacts the fastest and has the highest capacity of all. Both L-3404 and L-3406, having 2% bentonite binder, regenerated to their initial state following the reductive regeneration step. The lower rate of reaction for L-3406 is attributed to the use of pigment-grade iron oxide instead of catalyst-grade iron oxide as used in others. L-3407 and L-3409, both containing calcium aluminate cement binder, did not regenerate to their original state even after reductive regeneration. L-3770M (densified) and L-3769M (10% calcium sulfate binder) also exhibited high reactivity. However, L-3769M lost significant weight during reductive regeneration, probably as a result of sulfate binder decomposition.

Figure 5. TGA chemical reactivity for various zinc ferrite formulations.

Analysis of the first sulfidation in terms of fractional conversion is presented in Figure 6. Fractional conversion is defined as the pellet weight gain divided by the theoretical weight gain expected for the sulfidation of zinc ferrite only. Hence, the effect of differences in binder content among formulations is excluded as long as the binder is inert to reaction. All formulations in Figure 6 that were prepared in this program are designated L-xxxx, and meet the minimum chemical reactivity requirements stipulated in Criterion 2 (i.e., 50% conversion in 2 hours, and 70% total sulfur loading capacity). Also

Figure 6. Comparison of TGA fractional conversion with minimum requirements for the moving-bed system (0.5 fractional conversion in 2 hours).

included in Figure 6 is formulation T-2465M (2% bentonite binder), fabricated as a 20,000-lb batch under another DOE-sponsored program and included in the current program testing. Formulation L-2814 was previously fabricated and tested under GE internal funding and found to be extremely attrition resistant but lacked reactivity due to the presence of a high, 20% calcium aluminate, binder content. L-2814 represents the extreme case of a strong pellet with very little reactivity.

The difference in reactivity between first and second sulfidations for formulations containing bentonite and calcium aluminate is presented in Figure 7. There is practically no difference in reactivity for the first and second sulfidation of L-3404, containing 2% bentonite, while the difference is significant for L-3407, containing 3% bentonite and 12% calcium aluminate cement. Total sulfur analyses of L-3407 showed 36.4% after the first sulfidation, 9.98% after the first reductive regeneration, and 34.45% after the second sulfidation. These results indicate that the failure of L-3407 to regain its original weight after the first regeneration is possibly because of formation of stable calcium-sulfur species. However, the presence of residual sulfur species in L-3407 does not preclude its use in bench-scale testing since the sorbent still has 70% of the theoretical sulfur capacity and performance depends both on total sulfur capacity as well as mechanical strength (which is very high for this formulation). The total carbon content for the first sulfidation, first regeneration, and second sulfidation was 0.07%, 0.24%, and 0.09%, respectively. Further assessment of carbon and sulfur contents in sorbents subjected to multicycle testing is given in Section 4, Bench-Scale Analysis.

TGA tests were made on additional formulations not shown in Figures 5 to 7. Table 4 summarizes the TGA chemical reactivity for these other formulations that, in some cases, was unsatisfactory or very marginal. For instance, L-2814 was tested for two cycles of sulfidation and regeneration. During oxidative regeneration the sorbent gained weight indicating competing reaction of sulfation and sulfide to oxide conversion with sulfation dominating. In an attempt to decompose the sulfate, the temperature

Figure 7. Comparison of first and second sulfidation TGA reactivity for L-3404 and L-3407.

during the first oxidative regeneration was briefly raised to around 710 °C from the normal 675 °C. This, however, did not help to decompose the sulfate. The sorbent lost weight rapidly during reductive regenerations but only down to around 105% of its original starting weight. This indicated that the calcium aluminate portion of the sorbent was permanently converted to a sulfur-containing compound that did not regenerate under the GE reducing gas used.

Table 4. TGA Reactivity for Additional Zinc Ferrite Formulations

Formulation	Theoretical Sulfur Capacity (g S/100 g)	Fractional Conversion After 2-hr Sulfidation
L-3407 (1550 °F)	36.4	0.60
L-3467B	36.2	0.49
L-2814	31.9	0.26

Mercury porosimetry data for fresh, sulfided and regenerated sorbents extracted from the TGA are shown in Table 5. Comparison of values in this table shows that pore volumes decrease during sulfidation, as a result of formation of sulfide, for all formulations. During sulfidation, the smaller oxygen atom in the zinc ferrite spinel structure is replaced by a larger sulfur atom. Those formulations that exhibited good regenerability regained most of the existing pore volume measured when fresh. Those formulations with residual sulfur after regeneration, (such as L-3409, L-3407, and L-2814) did not regain the available pore volumes. Note in particular for L-2814, which did not meet the minimum TGA chemical reactivity requirement, that its original pore volume is not restored after the first reductive regeneration indicating sulfur retention.

Table 5. Porosimetry Data from TGA Zinc Ferrite Samples

Sorbent	Fresh		Sulfided		Regenerated	
	SPV(cc/g)	MPD(Å)	SPV(cc/g)	MPD(Å)	SPV(cc/g)	MPD(Å)
L-3404 (1550 °F)	0.23		0.132		0.239	
L-3406 (1550 °F)	0.24		0.142		0.217	
L-3407 (1550 °F)	0.24*		0.139		0.192	
L-3407 (1750 °F)	0.25		0.143		0.203	
L-3409 (1550 °F)	0.23		0.153		0.174	
					0.205**	
L-2814	0.21	719	0.14	575	0.160	555
L-3769M	0.219	2088	0.154	2567	0.242	1737
L-3770M	0.186	1960	0.127	2152	0.193	2007
T-2465M	0.20	1958	0.109			

* As provided by UCI

** After second reductive regeneration at 850 °F

However, not all changes in SPV and MPD are explained by the chemistry of sulfidation and regeneration of zinc ferrite. The binder is also important in determining the pore structure. Table 5 also shows that in some cases, as in L-3770M (i.e., densified formulation, bentonite binder), the changes in both SPV and MPD after the first complete regeneration are very insignificant pointing to the fact that bentonite is a very stable binder at high temperatures. In other cases, as in L-3769M (10% calcium sulfate binder), the SPV increases and the MPD decreases, both approximately by 12% after the first cycle, which could be a result of calcium sulfate decomposition. Similar to regeneration, as sulfate decomposes, more void volume is created (hence, SPV increases) and the void volume is created as small pores (hence, MPD decreases). This scenario is consistent with the loss of weight observed during TGA reductive regeneration in Figure 5.

Sulfur retention or changes in pore structure and chemical reactivity can not be considered totally undesired, as observed in single-pellet testing. Retained non-reactive sulfur can add strength to the pellet and opening of the pore structure can increase reactivity by decreasing pore diffusion, as will be presented in Section 4, Bench-Scale Testing.

2.3.3 Mechanical strength

Formulations that met Criterion 1 minimum requirements were subjected to mechanical strength testing, i.e., crush strength and attrition resistance measurements. The results of attrition resistance of fresh sorbents at 70 °F and at 1000 °F are given in Figure 8. These measurements were made according to ASTM D4058-81 (30 min. rotation at 60 rpm) for both 70 °F and 1000 °F measurements. The only variable being temperature. Attrition resistance at 1000 °F is slightly higher compared to ambient conditions for all cases studied, a favorable result for the intended moving-bed process.

The baseline formulation T-2465, prepared as cylindrical extrudates using 2% bentonite binder, exhibited an attrition resistance of 88.8%, as shown in the same figure. L-3404 and T-2465M, both also having the same chemical composition as T-2465 but rounded using laboratory-scale and pilot-scale equipment, respectively, exhibited significantly higher attrition resistance. The slight difference between the two rounded formulations, T-2465M and L-3404, may be attributable to the scale of equipment and/or repeatability of formulation procedures.

Figure 8. Attrition resistance of zinc ferrite formulations at 70 °F and 1000 °F.

To determine the correlation between attrition resistance for times other than 30 minutes, a series of tests, varying the attrition time, were conducted on T-2465M (Figure 9). Two cases were considered in Figure 9: one in which the fines produced were removed from the rotating cylinder at 30-minute intervals (case labelled "with fines removal", and the case where both sorbent and fines were returned to the rotating cylinder after each measurement (case labelled "without fines removal"). The change in attrition resistance with respect to time, or attrition rate, is different for the case of fines removal than for the case of no removal at all. For the case of fines removal, where the sorbent sample was rotated in 30 minute increments and the amount of fines (powder less than -20 mesh) removed at the end of each increment, a straight-line relationship exists between attrition resistance and time (i.e., a constant slope or attrition rate). For this case, attrition resistance for early times can be used to predict attrition losses, or equivalent attrition resistance, for longer times.

For the case of no fines removal, attrition resistance become constant and attrition rate goes to zero. In this case, attrition rates at early times (e.g., 30 minutes) cannot be used to extrapolate linearly to very long times (e.g., days) during multicycle testing. The difference between the two cases is a result of the dampening of shear and impact stresses experienced by the pellets when fines are always present in the rotating cylinder.

2.3.4 Application of Criterion 2

Application of Criterion 2 to formulations tested for TGA chemical reactivity and mechanical strength identifies those to be further studied in the bench-scale reactor system. All formulations that met Criterion 1, with the exception of L-2814, surpassed the minimum criteria for single pellet chemical reac-

Figure 9. Attrition resistance of T-2465M at 70 °F for various test durations with and without fines removal.

tivity of Criterion 2. Not all formulations that met mechanical strength requirements under Criterion 1 met the 94% target attrition resistance and the 20 lb/pellet minimum crush strength under Criterion 2. From those that surpassed all requirements under Criterion 2, five rounded formulations were selected for bench-scale testing in a packed bed reactor that simulated GE moving-bed conditions:

- L-3404: Containing 2% bentonite binder, calcined at 1550 °F, and prepared as a 1-gallon batch in laboratory-size equipment.
- L-3407: Containing 3% bentonite and 12% calcium aluminate cement binder, calcined at 1750 °F, and prepared as a 1-gallon batch in laboratory-size equipment.
- T-2465M: Containing 2% bentonite binder, calcined at 1550 °F, and prepared as a 20,000-lb batch using pilot-scale equipment.
- L-3769M: Containing 2% bentonite and 10% calcium sulfate binders, calcined at 1450 °F, and prepared as a 1-gallon batch in laboratory-size equipment.
- L-3770M: Containing 2% bentonite, calcined at 1450 °F, prepared as a densified formulation (i.e., having been rounded twice) in 1-gallon batch in laboratory-size equipment.

SECTION 3

PROVISION OF BENCH-SCALE UNIT

The bench-scale unit was designed and built to carry out bench-scale testing of sorbent formulations in three reactor vessels operated in parallel. The unit consists of three sections: gas-handling system, reactor system, and gas-analysis instrumentation. The schematic diagram of the unit is presented in Figure 10. A description of each system follows.

Figure 10. Schematic diagram of the bench-scale reactor system.

3.1 Gas Handling System

Gases from compressed gas cylinders are mixed in a manifold. All gas lines in the system are 304 stainless steel of either 1/4 in. or 3/8 in. nominal diameter. Toxic gases (CO, and H₂S) are located in a gas cabinet having a separate ventilation system and its own valving and purging manifold so as to vent the gases safely in the event of a leak. The gas-mixing manifold and reactor systems are located in two adjacent laboratory hoods that meet safety requirements for suction of highly toxic gases (i.e., those with 0-20 ppm threshold limit in breathing air).

The gas mixing manifold has a set of high-flowrate rotameters (up to 22 standard liters per minute, slpm, each) that are used to provide the flow for the three reactors operating at space velocities near 2000 hr⁻¹ each. Except for a relatively high H₂S concentration, gas compositions simulate the GE-CRD air-blown gasifier coal gas for the sulfidation reaction containing H₂S, H₂, CO, CO₂, H₂O, and N₂. Regeneration gases contain air, and N₂. Table 6 presents concentrations for each of the gases.

Table 6. Bench-Scale Unit Test Conditions

		Absorption	Oxidative Regeneration
Temperature	(°F)	1000	1000-1400
Pressure	(atm)	1	1
CO	(%)	8.0	-
CO ₂	(%)	11.0	-
H ₂	(%)	16.0	-
H ₂ O	(%)	30.0	-
H ₂ S	(%)	1.0	-
N ₂	(%)	34.0	balance
O ₂	(%)	-	1-21

A bypass line to the reactors allows determination by GC analysis of the exact gas mixture composition before and after the reactors. Two separate stainless steel lines were included for absorption or regeneration gases. Since the goal of the bench-scale testing is to mimic the configuration and operation of the GE moving-bed system, absorption and regeneration gases flowed in the same direction through each reactor.

Calculated total gas flowrate for each of the three reactors is 21.45 slpm of which 5.17 cc water/min per reactor are injected into the system through a water pump to generate the desired amount of steam. This flowrate corresponds to a space velocity of 2000 hr⁻¹ for a sorbent bed 2.5 in. in diameter and 8 in. in length. The mixed gases and the low-temperature water vapor are heated through a gas preheater and then distributed to the three reactors. Inlet flow to the reactors is controlled by a set of two high-temperature valves installed at the top and bottom of each reactor: the one at the top controlling the flowrate of gases and the other at the bottom selecting the appropriate gas lines (absorption/regeneration operation).

3.2 Reactor System

The reactor vessels were fabricated of 304 stainless steel at GE-CRD, and alonized (i.e., plasma sprayed with corrosion-resistant aluminum-based coating) by Alon Processing, Inc. (Pittsburgh, PA). A schematic of the reactor vessel is shown in Figure 11. Each reactor vessel is 2.5 in. in internal diameter. A hollow flange and bottom-end piece are welded to the 10-in. reactor cylinder, which rests on a support lip of the tube furnace. Alumina beads are used as heat transfer medium above and below the sorbent bed which is loaded through the hollow flange center opening. A metal "O" ring or a ceramic high-temperature gasket provides the seal between the hollow flange and the upper blind flange that closes the reactor vessel. The upper blind flange contains Swagelok-fitting threaded holes for a maximum of sixteen thermocouples per reactor. Differential pressure manometers monitor the pressure drop across the sorbent bed to determine if sorbent physical deterioration or accumulation of fine particulates takes places inside the reactor bed. Inlet lines to the reactor are heat traced from the gas preheater to each reactor using heavy-insulated Samoy flexible heating tapes rated at 1400 °F maximum. Thermocouples are positioned in the sorbent bed such that a minimum of four axial center-bed temperatures and four axial wall temperatures (axially spaced 2 inches apart) are continuously monitored.

Figure 11. Schematic diagram of the reactor vessel.

3.3 Gas Analysis System

Particulates in the reactor-exit absorption gases are collected using microfiber Balston Type 30/12 high-temperature filter tubes encased in a filter housing. These filter tubes were selected for removal of particles greater than $0.1 \mu\text{m}$ to ensure that gas lines leading to the gas analysis instrumentation remained free of solid contaminants. The filter housings are located at the exit of the reactor and outside of the furnace. Following the particulate removal, the gases flow through a set of 12 in. long water-cooled stainless steel condensers for water removal.

During absorption and regeneration, gases are analyzed by a gas chromatograph equipped with a flame photometric detector (GC/FPD) for low concentrations of sulfur species ($\text{H}_2\text{S} < 200 \text{ ppmv}$, $\text{SO}_2 < 1000 \text{ ppmv}$), by a gas chromatograph with a thermal conductivity detector (GC/TCD) for higher concentrations ($\text{H}_2\text{S} > 300 \text{ ppmv}$, $\text{SO}_2 > , \text{CO} > 500 \text{ ppmv}$, $\text{CO}_2 > 500 \text{ ppmv}$, $\text{H}_2 > 1000 \text{ ppmv}$), and by a Dupont photometric SO_2 analyzer (0-2000 ppmv). Teflon tubing (1/4 and 1/16 in. I.D.) is used for all gas analysis sampling lines to minimize adsorption and contamination of sulfur species in the lines between water condenser and gas analysis instrumentation. Gases are bubbled through a solution of sodium hypochlorite (household bleach) to remove sulfur contaminants prior to venting through the exhaust hood.

Temperature measurements from the reactor thermocouples and gas lines are collected by a Hewlett-Packard data acquisition system. An in-house process control software package (TMGR) running on a HP 7933 computer processes the data and displays the graphical data on a computer terminal. The time-stamped information is stored on a magnetic tape for future retrieval.

SECTION 4

BENCH-SCALE TESTING

4.1 Bench-Scale Experimental Procedure

The bench-scale reactor unit described in Section 3 was used to carry out H₂S absorption from simulated coal gases and sorbent regeneration simulating a moving-bed scheme. Absorption was carried out at 1000 °F with an artificially high H₂S concentration (1% v/v), to accelerate the testing over 10 cycles. Gas compositions are shown in Table 7. The reaction was stopped when the reactor effluent H₂S concentration, or breakthrough concentration, reached 200 ppmv.

Table 7. Bench-Scale Reactor Test Conditions

		Absorption	Oxidative Regeneration
Temperature	(°F)	1000	1000-1400
Pressure	(atm)	1	1
CO	(%)	8.0	-
CO ₂	(%)	11.0	-
H ₂	(%)	16.0	-
H ₂ O	(%)	30.0	-
H ₂ S	(%)	1.0	-
N ₂	(%)	34.0	balance
O ₂	(%)	-	1-21

The oxidative regeneration was carried out nominally at 1000 °F simulating a scheme typical of the moving-bed system to control the temperature rise of the sorbent bed (triggered by the exothermic oxidation reactions) (Smith et al. 1987). Regeneration was started by diluting air in nitrogen (1-2% oxygen) maintaining the peak bed temperature below 1250 °F. Once the peak temperature in the bed began to decrease, the oxygen concentration was gradually increased to 7%, and finally to 21% (pure air) while maintaining a constant total gas flow and a minimum reactor wall temperature of 1000 °F. Finally, the temperature was raised to 1400 °F to decompose any sulfate formed in the course of regeneration.

4.2 Bench-Scale Results

Five formulations were tested for ten cycles of absorption and regeneration in the bench-scale reactor system. These five formulations, all of which met minimum requirements imposed by Criteria 1 and 2, are: L-3404, L-3407, T-2465M, L-3769M, and L-3770M.

Figure 12 shows the reactor effluent H₂S concentration as a function of time, or breakthrough curve, for each of the first three sorbents tested for 10 cycles of absorption and regeneration. Breakthrough is defined as the point at which effluent H₂S concentration reached 200 ppmv. H₂S concentrations prior to breakthrough were measured in the range of 5 to 10 ppmv for L-3404 and T-2465M, and 10 to

15 ppmv for L-3407, and were near equilibrium values for H₂S at the test conditions.

Shown in the lower x-axis scale of each breakthrough curve is the dimensionless time, which provides a measure of the overall sorbent bed utilization (in terms of sulfur capture) relative to that at the calculated bed saturation time (from H₂S flow rate and mass of zinc ferrite in the bed). The dimensionless time in packed bed tests allows us to normalize sorbent performance and eliminate differences in inert binder content in order to bring out differences in sorbent reactivity due to pellet pore structure. All reactors contained the same volume of sorbent but different amounts of zinc ferrite due to differences in density and inert binder content. As seen in Figure 12, bed utilization at the 200 ppmv H₂S breakthrough time for the first three formulations ranges from 27 to 30% for L-3404, from 20% to 28% for T-2465M, and from 5% to 11% for L-3407.

Figure 13 shows similar breakthrough plots for formulations L-3769M and L-3770M (densified). At the 200 ppmv breakthrough time, the dimensionless time ranges from 13 to 25% for L-3769M and from 10 to 13% for L-3770M. The reactor effluent H₂S concentration was measured around 3-10 ppmv for L-3769M and around 6-7 ppmv for L-3770M. The low pre-breakthrough outlet H₂S concentrations measured in all five formulations represent excellent sulfur removal, near 99.9% based on the 1% H₂S inlet gas. The low H₂S levels measured in these tests are close to the limits reported for thermodynamic vapor/solid equilibria between H₂S gas and ZnO/ZnFe₂O₄.

The dimensionless time at breakthrough, which is proportional to the amount of sulfur captured up to breakthrough, followed the relationship: L-3407 < L-3770M < L-3769M < T-2465M < L-3404. In general, this trend is explained by changes in specific pore volumes (SPV) of the sorbents before and after bench-scale testing, as shown below:

	L-3407	< L-3770M	< L-3769M	< T-2465M	< L-3404
% Total binder	15	2	12	2	2
SPV Fresh, cc/g	0.25	0.19	0.22	0.20	0.23
SPV 10-cycle test, cc/g	0.21	0.19	0.17	0.20	0.22

On the one hand, L-3404 has the highest dimensionless time at breakthrough (i.e., highest sulfur capacity) and, generally speaking, the highest specific pore volume as fresh and cycled sorbent. On the other hand, L-3407 has the lowest dimensionless time and a significant loss in specific pore volume. Having 12% calcium aluminate binder, in addition to 3% bentonite, is probably the cause of the loss in reactivity of L-3407. L-3770M has the lowest specific pore volume of those formulations containing 2% bentonite binder and exhibits a lower dimensionless time at breakthrough than the other two 2%-bentonite formulations. A more detailed discussion and analysis of chemical and mechanical properties of cycled sorbents will be given in Section 5, Bench-Scale Analysis.

Based on breakthrough curve performance alone, a desirable sorbent should display high reactivity for sulfur absorption (as given by a high dimensionless time) and minimal deterioration of chemical reactivity (as given by constant or increasing dimensionless times with increasing cycle number). Formulation L-3404 exhibited the highest initial reactivity while L-3407 showed the lowest reactivity and most pronounced chemical deterioration. The sorbent utilization for the formulations tested is expected to be higher for commercial systems where much larger reactor beds are employed and the smaller ratio of pellet diameter to reactor diameter will minimize potential gas bypassing or

Figure 12. H₂S breakthrough curves for L-3404, T-2465M, and L-3407 zinc ferrite sorbents.

Figure 13. H_2S breakthrough curves for L-3769M and L-3770M zinc ferrite formulations.

channeling. Zinc ferrite sorbents with higher bed utilization, typically 40% or higher, have been manufactured in the past and tested (Grindley et al. 1985) but at the expense of being weaker or softer and, hence, less suitable for long-term operation in moving-bed systems. In addition to breakthrough performance, the mechanical strength of pellets extracted from the reactor vessels must be considered before choosing the best formulation for moving bed applications.

During regeneration, temperature and outlet SO₂ concentration were monitored as functions of time to control the level of regeneration achieved at each of the simulated stages of regeneration in a moving-bed system. Regeneration as initially planned called for introduction of SO₂, in addition to air and nitrogen, to give a mixture of 1% oxygen, 12% sulfur dioxide, and balance nitrogen; however, excessive amounts of elemental sulfur as yellow powder deposited on the internal surfaces of the system, downstream from the reactor bed. This result is expected since initial regeneration with 1% oxygen rapidly consumes the oxygen at the reactor inlet and SO₂ readily reacts with the sulfided sorbent via one of several reaction paths, for instance,

To prevent damage to the gas analysis instrumentation by elemental sulfur, SO₂ addition to the inlet regeneration gas was eliminated. Figure 14 shows typical temperatures measured at the center of the reactor bed for T-2465M during oxidative regeneration. From the beginning of regeneration to the final temperature ramp, the maximum bed temperature was maintained below 1250 °F.

Figure 15 presents typical reactor effluent SO₂ concentrations during oxidative regeneration of L-3770M. Outlet SO₂ concentration increases to an average of 1.8% when 4% oxygen enters the reactor. A theoretical value of 2.5% SO₂ is predicted from the stoichiometry of the oxidation of ZnS and FeS. We ascribe this difference in concentrations to zinc sulfate formation and, to a lesser extent, elemental sulfur formation (which forms a powdery yellow film on the water condenser walls). Regeneration appears to be complete after 300 minutes, when SO₂ concentrations have declined to near 300 ppm. Nonetheless, an increase in effluent SO₂ (up to 0.35%) is observed upon heating the bed from 1000 to 1400°F. This, of course, is likely caused by thermal decomposition of ZnSO₄ (thermal decomposition temperature: 1112-1200 °F). The maximum bed temperature of 1400 °F was maintained for 45 to 60 minutes during which the SO₂ concentration remained constant at around 0.13%. Upon cooling of the bed to 1000 °F, the SO₂ concentration decreased accordingly.

In order to determine if zinc sulfate is still present at the end of the oxidative regeneration, simultaneous measurements of SO₂ and H₂S effluent concentrations were periodically made during the subsequent reductive regeneration. Inlet gas composition was the same as in absorption runs except for the absence of H₂S. Figures 16 and 17 show the effluent concentration of these two species plotted against time during reductive regeneration. Figure 16 presents the results for L-3769M (10% calcium sulfate binder). An initial burst of SO₂, up to 3010 ppm for this particular run, was measured during the first two minutes and decreased very fast thereafter. The initial SO₂ burst was always observed and measured up to near 4000 ppmv for several runs. Figure 17 presents the results of reductive regeneration of L-3770M (densified) where the SO₂ peak was measured only at 762 ppm.

The burst of SO₂ indicates that all zinc sulfate was not completely decomposed during the 60-min 1400 °F temperature plateau in both cases. The higher value of the SO₂ peak for L-3769M may probably be caused by decomposition of the calcium sulfate binder under reducing conditions of H₂ and

Figure 14. Reactor bed center temperatures for regeneration of T-2465M.

Figure 15. Reactor outlet SO₂ concentration during oxidative regeneration of L-3770M.

Figure 16. SO_2 and H_2S reactor outlet concentrations during reductive regeneration of L-3769M.

CO (TGA results for L-3769M previously presented in Figure 5 showed weight losses during reductive regeneration, a strong evidence for sulfate decomposition). However, the measurements in bench-scale testing may not necessarily be the peak concentrations, since they are discrete measurements by gas chromatography. H_2S levels in both Figures 16 and 17 are one order of magnitude lower than those for SO_2 and follow the same decreasing trend as SO_2 . The presence of H_2S in the reducing gas is also a product of decomposition of sulfur species in the sorbent.

Figure 17. SO₂ and H₂S reactor outlet concentrations during reductive regeneration of L-3770M.

SECTION 5

BENCH-SCALE ANALYSIS

Samples of sorbents tested in the bench-scale reactor system were obtained at the end of the 10th absorption and at the end of the 10th oxidative regeneration. The following section describes the analyses performed on those cycled sorbent samples.

5.1 Single Pellet TGA Chemical Reactivity

Figure 18 shows the results of TGA chemical reactivity of cycled sorbents in terms of normalized weight fraction as a function of time for the first three formulations: L-3404, L-3407, and T-2465M. These tests were performed on single pellets in the fresh state and on cycled pellets (i.e., 10th cycle regenerated) extracted from two locations in the reactor bed (i.e., gas inlet and gas outlet locations) for the three sorbents. The gas inlet location was the most heavily reacted location of the bed at each cycle. Looking at Figure 18 cycled L-3404 and cycled T-2465M exhibited slightly higher, although still comparable, chemical reactivity than the corresponding fresh pellet. L-3407, on the other hand, showed significantly lower reactivity under the same test conditions. Both cycled L-3404 and T-2465M exceeded the 0.5 fractional conversion in 2 hours that was used to screen fresh pellets. Cycled L-3407, on the other hand, does not meet this minimum criterion. The decrease in pellet weight during the 30-minute reductive regeneration observed in the regenerated cycled pellets but not on the fresh pellets was probably caused by reduction of Fe_2O_3 to Fe_3O_4 . The binder, bentonite, is believed to provide resistance to reduction initially, thus the fresh pellet does not show measurable reduction. Some weight change during reduction is also attributable to sulfate decomposition, but this is small as will be demonstrated from sulfate measurements from the pellets.

Figure 19 shows the corresponding TGA chemical reactivity for L-3769M and L-3770M. L-3769M exhibits a chemical reactivity after 10 cycles that is even higher than that of the fresh sorbent. L-3770M, on the other hand, has a chemical reactivity significantly lower than that of the fresh material. After adjusting for binder content in each formulation, L-3769M exceeds the 0.5 fractional conversion in 2 hours after bench-scale testing while L-3770M does not. Obviously, L-3770M has experienced a loss in chemical reactivity during bench-scale testing.

5.2 Pellet Physical Morphology

The specific pore volume of fresh samples and those extracted from the gas inlet location after the 10th absorption and the tenth oxidative regeneration are presented in Table 8. The difference in reactivity among T-2465M, L-3404, and L-3770M, all three containing 2% bentonite binder, is a result of differences in pellet pore morphology. As shown in Table 8, L-3404 has a higher specific pore volume than T-2465M and L-3770M for the fresh and cycled (10th absorption, and 10th regeneration) material. Hence, L-3404 would be expected to have the oxide more readily available for chemical reaction and a higher rate of sulfur absorption than the other two. This was the case observed during bench-scale testing as previously shown in Section 4. L-3407 and L-3769M, both containing other binders in addition to bentonite, do not follow a trend of pore characteristics and chemical reactivity. The chemical nature of the binder and the interactions of it with the sulfur species, which are not easily explainable, appear to be as important as the pore structure for the purpose of sulfur absorption. More needs to be learned about the interaction between calcium binders and oxide sorbent.

Figure 18. TGA chemical reactivity of L-3404, T-2465M, and L-3407 sorbents extracted from the bench-scale reactor system after the 10th oxidative regeneration.

Figure 19. TGA chemical reactivity of L-3769M and L-3770M sorbents extracted from the bench-scale reactor system after the 10th oxidative regeneration.

Table 8. Pore Characterization of Bench-Scale Reactor Sorbents*

	Specific Pore Volume (cc/g)	Median Pore Diameter (Å)
L-3404:		
Fresh	0.23	2648
10 th Absorption (Gas Inlet)	0.17	3650
10 th Ox. Regeneration (Gas Inlet)	0.22	2700
T-2465M:		
Fresh	0.20	1958
10 th Absorption (Gas Inlet)	0.16	3056
10 th Ox. Regeneration (Gas Inlet)	0.20	2756
L-3407:		
Fresh	0.25	2126
10 th Absorption (Gas Inlet)	0.22	2283
10 th Ox. Regeneration (Gas Inlet)	0.21	2221
L-3769M:		
Fresh	0.22	2088
10 th Absorption (Gas Inlet)	0.13	7382
10 th Ox. Regeneration (Gas Inlet)	0.17	2902
L-3770M:		
Fresh	0.19	1960
10 th Absorption (Gas Inlet)	0.15	3286
10 th Ox. Regeneration (Gas Inlet)	0.19	3051

*As measured by RTI.

5.3 Sorbent Mechanical Strength

Attrition resistance and crush strength of sorbent samples extracted from three reactor bed locations (i.e., gas inlet, middle, and gas outlet sections) after the tenth cycle are presented in Figures 20 and 21. Referring to Figure 20 for the samples after the 10th regeneration, the attrition resistance was generally lower at the gas inlet, where the highest degree of absorption-regeneration cycling took place, and highest at the gas outlet where the opposite was true. This indicates that the rate of attrition increases with degree of reaction, as a result of chemical transformations between sulfided and regenerated states of the sorbent, and temperature changes during exothermic regeneration. Also shown in Figure 20 is the crush strength for the same five regenerated sorbents. Crush strength of sorbents containing bentonite only as a binder (T-2465M, L-3404, and L-3770M) was significantly lower than that of the fresh sorbent, and was practically constant at all three bed locations. Unlike the behavior of crush strength for bentonite-only sorbents, the crush strength of L-3407 and L-3769M, both containing calcium binders in addition to bentonite, was maintained or even increased after the 10-cycle testing. With this observation in mind, Figure 20 does show a good correlation between high attrition resistance and high crush strength.

ASTM D4058-81 (30 MIN/60 RPM/ 70 F)

70 F

Figure 20. Attrition resistance and crush strength of five sorbents extracted from the bench-scale reactor system after the 10th oxidative regeneration.

Figure 21. Attrition resistance and crush strength of five sorbents extracted from the bench-scale reactor system after the 10th absorption.

The more extensive chemical transformations due to sulfidations experienced by the bentonite-only sorbents at each cycle are very likely to produce internal stresses that reduce crush strength but apparently do not seem to affect the attrition resistance as measured by the ASTM method. However, the measurement of attrition resistance using a 20 mesh sieve according to the ASTM procedure does not give a complete picture of the extent of attrition and breakage experienced by the sorbent pellets. Bentonite-only containing sorbents (T-2465M and L-3404, for instance) turned into a very large fraction of pellet pieces larger than 20 mesh after the test; these pellet pieces, or granules as they will be called from now on, ranged mostly between 1 and 5 mm (16 to 4 mesh) in diameter. Whole pellets were almost nonexistent in the samples extracted from the attrition tester. These granules result from breakage and crumbling of pellets and are not considered attrition losses by ASTM D4058-81 definition since they are larger than 20 mesh (0.841 mm). On the other hand, L-3407 and L-3769M pellets did not generally break into granules and the samples were generally whole pellets, smaller in size, and fine dust (which is certainly considered part of attrition losses). The conclusion is that attrition resistance as described by the ASTM test does not distinguish between whole pellets and a distribution of large broken pieces or granules. Consequently, the apparent observation of high attrition resistance/low crush strength for L-3404 is not strictly correct since the oversize contains fewer whole pellets. A distribution of sizes and modification of the definition of attrition loss to include a size distribution is necessary to better characterize sorbents.

Attrition resistance and crush strength tests were also conducted on cycled sorbents after the 10th absorption (Figure 21). Here the attrition resistance tests were conducted over 4 hours, instead of standard time of 30 minutes. As expected, the mechanical strength of sulfided pellets increases with respect to fresh sorbent as a result of the decrease in specific pore volume inside the pellet. No further concern is necessary for the mechanical integrity of sulfided pellets since, as shown here, regenerated pellets are the weaker stage of the sorbent and more likely to suffer breakage and attrition during transport in a moving-bed system.

In addition to pellet size characterization, the effect of chemical transformations on pore structure is important to explain mechanical strength during cycling. This observation is explained by referring to Table 8 and noticing that the specific pore volume of the regenerated L-3407, which had low reactivity at the end of the cyclic testing, decreased substantially during testing, from 0.25 to 0.21 cm³/g.

Overall, results of mechanical strength indicate that attrition resistance and crush strength are two properties of the pellet sorbent that are related. The standard ASTM D4058-81 test that defines attrition losses based on a 20 mesh sieve does not account for pellet breakage into granules larger than 20 mesh or any size distribution of these granules. For the specific case of moving-bed systems, transport of pellets from vessel to vessel produces continuous abrasion among pellets and walls, hence requiring high attrition resistance, and some crushing of pellets upon actuation of valves, resulting in compression loads; attrition resistance and crush strength are both important.

5.4 Pellet Chemical Composition

Chemical analyses of sorbent samples extracted from three reactor bed locations (gas inlet, middle, and gas outlet) are shown in Tables 9 and 10. Looking first at Table 9, where the results of the sulfided sorbent after the 10th absorption are presented, one can see that there is no trend in the carbon content as a function of location in the reactor bed which is approximately constant at less than 0.2% for all cases. Hence, excessive carbon deposition is not a concern for the reactor conditions used in these tests.

Table 9. Chemical Analysis of Bench-Scale Sorbents
10th Absorption

	Total C %	Total S %	Sulfur Loading (g S/100 g Fresh Sorbent)	% of Theoretical Sorbent Utilization
L-3404:				
Gas Inlet	0.06	18.80	20.03	50.81
Middle Section	0.07	14.50	15.22	38.30
Gas Outlet	0.06	8.79	9.05	22.47
Average	0.06	14.03	14.77	37.16
T-2465M:				
Gas Inlet	0.08	11.30	11.73	28.82
Middle Section	0.10	12.10	12.60	31.10
Gas Outlet	0.16	1.19	1.19	2.15
Average	0.11	8.20	8.51	20.69
L-3407:				
Gas Inlet	0.20	5.67	5.76	9.57
Middle Section	0.18	5.02	5.09	7.27
Gas Outlet	0.21	3.32	3.35	2.36
Average	0.20	4.67	4.73	6.40
L-3769M:				
Gas Inlet	0.37	12.03	12.47	27.71
Middle Section	0.40	11.50	11.90	25.96
Gas Outlet	0.55	5.20	5.29	8.43
Average	0.44	9.58	9.89	21.03
L-3770M:				
Gas Inlet	0.04	7.04	7.21	16.63
Middle Section	0.03	6.50	6.64	14.37
Gas Outlet	0.01	3.10	3.13	6.46
Average	0.03	5.55	5.66	12.49

With respect to sulfur content, higher sulfur uptakes are observed at the gas inlet locations. The total sulfur content of the five sorbents correlates very well with the TGA single pellet reactivity of fresh pellets (L-3404 > T-2465M > L-3769M > L-3770M > L-3407) and with the measured dimensionless time during bench-scale testing. Measured at breakthrough, sulfided L-3404 has a higher average sulfur uptake (14.03%) than T-2465M (8.20%) and both exhibit high uptakes at the gas inlet and middle section locations, indicating that the effective reaction rate is very fast and the reaction front length is much less than then the physical length of the bed (i.e., 8 inches). L-3407, on the other hand, has a lower sulfur content for the gas inlet section and it decreases more gradually to the gas outlet. Hence,

the reaction front length is not small when compared to the bed length. Also in Table 9, the total sulfur uptake, column 3, is expressed as grams of sulfur/100 g of fresh sorbent in column 4 under Sulfur Loading.

The last column in Table 9 shows the % sorbent utilization which is calculated by subtracting the residual sulfur in the regenerated sorbent (Table 10) from the sulfur in the sulfided sorbent and the result divided by the theoretical sulfur capacity of zinc ferrite (after adjusting for binder content). The % sorbent utilization then accounts for net sulfur uptake during absorption and excludes nonregenerable sulfur. Values of % sorbent utilization compare fairly well with the dimensionless times calculated from H₂S breakthrough curves during bench-scale testing (Section 4). For instance, the average bed utilization of T-2465M is 20.7% and the corresponding calculated dimensionless time is 0.20 or 20%. Similar results are found for L-3407 (6.4% av. bed utilization, 0.05 or 5% dimensionless time), L-3769M (21% av. bed utilization, 0.15 or 15% dimensionless time), L-3770M (12.5% av. bed utilization, 0.10 or 10% dimensionless time). L-3404 (37% av. bed utilization, 0.3 or 30% dimensionless time) did not show as good a match. In all cases the calculated dimensionless time is always less than the bed utilization estimated from measured sulfur content of pellets extracted from the bed.

Chemical analyses of the regenerated sorbents are shown in Table 10. All formulations tested contained similar, but not significant, amounts of residual carbon (less than 0.10%) after the tenth oxidative regeneration. These amounts of residual carbon in the regenerated samples do not preclude the use of the sorbent formulations for high-temperature desulfurization. The amounts of total and residual sulfur also are shown in Table 10. The percent residual sulfur is obtained by subtracting the sulfur present originally in the binder from the total sulfur in the pellet after the 10th oxidative regeneration. Except for L-3769M, which contains 10% calcium sulfate binder (or 2.35% S in the binder), L-3407 is the formulation that contained much higher amounts of residual sulfur. L-3407 was found to contain lower ratios of sulfates to total sulfur even though the residual sulfur content was much higher (about 2.55%) than the other sorbents (1.0% or less). This difference is probably the result of reaction between the 10% calcium aluminate binder and the gas-phase sulfur compounds, SO₂ or H₂S, during absorption or regeneration to form calcium-sulfur species. CaS and CaSO₄ are very stable species; for instance, CaSO₄ is thermally stable at temperatures below 2180 °F at 1 atm total pressure; hence, it would not decompose at the regeneration temperatures of 1000 to 1400 °F. CaS oxidation rates are not significant until temperatures near 2100 °F or higher are reached and depend on O₂ and SO₂ partial pressures (Torres-Ordoñez et al. 1989).

In addition to average pellet composition, the distribution of iron, zinc, and sulfur was obtained to determine the extent of zinc evaporation and sulfur retention distribution within the pellets. Scanning electron microscopy of cycled pellets after the 10th oxidative regeneration were performed on L-3407 (gas inlet) and L-3404 (gas inlet) samples. Iron, zinc, and sulfur maps were also obtained using SEM with energy dispersive x-rays (EDX), and quantitative atomic composition of iron and zinc was obtained using SEM with electron microprobe analysis (EMA).

The EMA quantitative atomic compositions were measured using a defocused electron beam over several point locations of 20 μm in diameter for each measurement and are shown in Table 11 and Figure 22. Because of potential microscopic metal segregation in the pellets, several measurements were made, and the average calculated, for each of four pellet cross-section locations: center, middle, outer, and "glazed" regions. The "glazed" region corresponds to the outermost thin layer on the

Figure 22. SEM/EMA of L-3404 and L-3407 sorbent samples (gas inlet) extracted from the bench-scale reactor system after the 10th oxidative regeneration.

Table 10. Chemical Analysis of Bench-Scale Sorbents
10th Oxidative Regeneration

	% Total C	% Total S	% Residual S*	% Sulfate S	% $\frac{\text{Sulfate S}}{\text{Total S}}$
L-3404:					
Gas Inlet	0.03	0.20	0.20	0.13	65.0
Midsection	0.03	0.31	0.31		
Gas outlet	0.04	0.28	0.28	0.12	41.7
T-2465M:					
Gas Inlet	0.04	0.48	0.48	0.28	58.3
Midsection	0.06	0.46	0.46		
Gas outlet	0.05	0.35	0.35	0.08	22.9
L-3407:					
Gas Inlet	0.10	2.52	2.52	1.06	41.9
Midsection	0.06	2.63	2.63		
Gas Outlet	0.07	2.55	2.55	0.41	16.2
L-3769M:					
Gas Inlet	0.20	2.87	0.52	2.43	15.38
Middle Section	<0.02	2.56	0.21	2.48	61.90
Gas Outlet	0.06	2.37	0.02	1.13	0.00
L-3770M:					
Gas Inlet	0.01	0.72	0.72	0.33	45.8
Middle Section	0.03	1.03	1.03	0.63	61.2
Gas Outlet	0.02	0.61	0.61	0.42	68.9

*Excludes sulfur originally in the binder

pellet periphery where the mounting epoxy penetrated the porous pellet. Because pellet porosity decreases the absolute intensity of the diffracted energy signal, the reported results for zinc and iron concentrations as functions of radial location are presented below in the form of Zn:Fe ratios (which are independent of porosity).

Table 11. SEM/EMA Zn:Fe Ratio as Function of Pellet Radial Location

Sample	Glazed	Outer	Middle	Center	Average
<hr/>					
L-3404:					
fresh	0.492	0.489	0.503	0.495	0.495±0.006
10 th Ox. Regen.	0.385	0.294	0.821	0.679	
<hr/>					
L-3407:					
fresh	0.499	0.496	0.508	0.513	0.504±0.008
10 th Ox. Regen.	0.436	0.584	0.564	0.632	

The theoretical Zn:Fe ratio for zinc ferrite is 0.5, based on the zinc ferrite chemical structure, ZnFe_2O_4 . Measured Zn:Fe ratios for the fresh L-3404 and L-3407, as shown above, certainly agree with the expected value and show the accuracy of the SEM/EMA method for chemical analysis.

Comparison of cycled samples after the 10th. oxidative regeneration with fresh samples show that measurements in the glazed region (the outermost region in the pellet cross-section) and the outer region have lower Zn:Fe ratios while the middle and center measurements have higher ratios than the fresh values. The lower Zn:Fe ratios at the pellet periphery imply zinc losses due to evaporation but the lower values at the center locations indicate metal migration within the pellet.

The average pellet composition was also measured by x-ray fluorescence spectrometry (XRF) to determine whether the pellet as a whole had lost zinc or iron. Results are shown in Table 5.4-4. Average weight concentrations of ZnO over the whole pellet for both L-3404 and L-3407 indicate that, within the experimental error of the technique, there is no measurable loss of zinc between fresh and cycled pellets. Since SEM/EMA detected significant differences in zinc distribution across the pellet radius, then zinc migration rather than zinc losses due to evaporation seems to have taken place. Zinc migration would occur during regeneration, for instance, when the outer surface of the pellet is hotter (because of oxidation of sulfides) and the inner pores towards the center of the pellet are at a lower temperature (nominally at 1000 °F); gas phase concentration and temperature gradients would drive zinc vapor to the inner cooler pores where the vapor would then condense.

With respect to Fe concentration, Fe_2O_3 content of L-3407 decreases by about 2% in the cycled regenerated pellet from 57.1 to 55.3%. This suggests that some iron reduction, perhaps of Fe_2O_3 to FeO and Fe, has taken place. This conversion does not seem to have occurred in L-3404, nonetheless. SiO_2 comes from the bentonite binder while Al_2O_3 comes from both bentonite and calcium aluminate binders.

The conclusions concerning zinc losses due to evaporation versus zinc migration are, of course, applicable to the experimental conditions of bench-scale reactor testing that the sorbents were subjected here, namely, a high steam concentration in the simulated coal gas. Other test conditions may result in different experimental observations, of course.

Figure 23 shows the SEM/EDX maps for Fe, Zn, and S at the pellet midsection of regenerated L-3404. Fe is homogeneously distributed through the area while Zn and S show significant microscopic

PELLET SECTION 400X

SULFUR MAPPING 400X

IRON MAPPING 400X

ZINC MAPPING 400X

Figure 23. SEM/EDX Fe, Zn, and S maps of L-3404 sorbent sample (gas inlet) extracted from the bench-scale reactor system after the 10th absorption.

Table 12. XRF Average Pellet Composition of 10th
Regeneration Bench-Scale Reactor Sorbents*

Sample	L-3407 Fresh	L-3407 10 th Ox. Regen.	L-3404 Fresh	L-3404 10 th Ox. Regen.
Fe ₂ O ₃ *	57.1±0.3	55.3±0.3	64.3±0.3	64.4±0.3
ZnO*	30.3 ±0.3	29.9±0.3	33.1±0.3	33.1±0.3
SiO ₂ *	1.1±0.1	1.1±0.1	1.0±0.1	0.8±0.08
Al ₂ O ₃ *	7.9±0.2	7.9±0.2	0.8±0.08	0.8±0.08
Total wt. %	96.4	94.2	99.2	99.1
Zn:Fe Mol Ratio	0.521	0.531	0.505	0.504

* Values expressed as weight percentages

sulfur (Table 10) follows the distribution of zinc and is, very likely, zinc sulfate. On the other hand, Figure 24 shows homogeneous distribution of Fe, Zn, and S for equivalent pellet measurements on L-3407. Since L-3407 has the highest sulfur retention and lowest sulfate composition of the two under comparison, one can conclude that the sulfur retained in L-3407 is some form of calcium-sulfur species, perhaps including aluminum also. From the chemical analyses of regenerated pellets of L-3404 and L-3407 we can conclude that zinc losses due to evaporation have not been detected. Rather, a zinc migration towards the pellet center has been measured.

5.5 Application of Criterion 3 (Superior Formulation)

As explained in Section 1.4 Sorbent Screening Criteria, a sorbent formulation was to be selected under this program that exhibits superior properties of mechanical strength and chemical reactivity after extended bench-scale testing. Based on engineering experience, a measuring scale for this purpose was developed as part of Criterion 3, where equal weights were given to the mechanical strength and the chemical reactivity of the cycled sorbents to arrive at a measure of the overall performance P of a sorbent. A maximum score of 100 points each for mechanical strength, M.S., and chemical reactivity, C.R., can be earned by a formulation; hence, a total score P of 200 points are possible for each sorbent formulation. Overall performance is then defined by

$$P = M.S. + C.R. \quad (5-1)$$

Computation of mechanical strength, M.S., was done by using the following formulae

$$M.S. = 0.5(\%C_N) + 0.5(\%A_N) \quad (5-2)$$

where

$$\%C_N = W_C \frac{C_s}{C_{max}} \cdot 100; \quad \%A_N = W_A A_R \quad (5-3)$$

and

C_S = Crush strength, lb/pellet

PELLET SECTION 400X

SULFUR MAPPING 400X

IRON MAPPING 400X

ZINC MAPPING 400X

Figure 24. SEM/EDX Fe, Zn, and S maps of L-3407 sorbent sample (gas inlet) extracted from the bench-scale reactor system after the 10th absorption.

- $C_{\max}$ = Maximum desired crush strength, e.g., 30 lb/pellet
- W_C = Weighting factor for crush strength. Range: 0-1.
- C_N = Normalized crush strength. Range: 0-100 points.
- A_R = % Attrition resistance (based on ASTM D4058-81). Range: 0-100%
- W_A = Weighting factor for attrition resistance. Range: 0-1.
- A_N = Normalized attrition resistance. Range: 0-100 points.

As seen from Equation 5 – 1, 50% of the points are given for the mechanical strength and 50% for the chemical reactivity. The mechanical strength is composed of 50% normalized crush strength and 50% normalized attrition resistance for a total of 100 points.

The maximum desired crush strength, $C_{\max}$, was arbitrarily set to 30 lb/pellet since this value was above the measured crush strength of all formulations and is a good maximum target for moving-bed systems. The weighting factor for crush strength, W_C , accounts for differences in pellet size and shape and was set equal to 1 since all of the five bench-scale formulations are ellipsoidal pellets of approximately equal size. W_C would be different from 1 when comparing cylindrical extrudates, spherical pellets, and ellipsoidal pellets. The weighting factor for attrition resistance, W_A , accounts for pellet size differences observed after performance of ASTM D4058-81 test. As explained in Section 5.3 – Sorbent Mechanical Strength, this test defines attrition losses based on 20 mesh sieve as a cut-off point for undersize and oversize, and does not account for pellet size distributions due to pellet breakage into granules or aggregates greater than 20 mesh. Hence, we surmounted this limitation by setting

- $W_A = 1.0$ if more than 50% wt. of oversize (+20 mesh) is whole pellets.
- $W_A = 0.5$ if less than 50% wt. of oversize is granules or aggregates.

Because the 10th regenerated sorbent samples were always weaker in mechanical strength than the 10th absorption samples, mechanical strength requirements focused only on the regenerated samples.

Chemical reactivity of cycled sorbents was based on bench-scale breakthrough curves – i.e., dimensionless times – (Figures 12 and 13), average % sorbent utilization (from sulfur analyses of 10th absorption samples, Table 9, and TGA chemical reactivity of cycled regenerated sorbent samples (Figures 18 and 19). For all tests of chemical reactivity, the following trend was observed:

$$L-3407 < L-3770M < L-3769M < T-2465M < L-3404$$

The numerical value for the overall chemical reactivity of cycled sorbents to be used in Equation 5 – 1 was chosen to be the average % sorbent utilization (Table 9) since it is the measured average sulfur capacity (g sulfur/100 g sorbent) for the sorbent bed and a very useful parameter for absorber design considerations.

A summary of the sorbent performance with respect to mechanical strength and chemical reactivity is presented in Table 13 and Figure 25. As it can be seen, the long term durability, as measured by the overall performance P, is lower for sorbents containing only bentonite as binder (e.g., L3770M, T-2465M, and L-3404) and higher for those containing calcium binder (i.e., L3407 and L-3769M) in addition to bentonite. The superior formulation is then selected as the one that exhibits the best balance of chemical reactivity and mechanical strength, i.e., the highest value of overall performance P.

The selected superior formulation is thus L-3769M containing 10% calcium sulfate/2% bentonite binder and 88% zinc ferrite.

Table 13. Summary Data for Criterion 3

Formulation	C _S , lb/pellet	A _R , %	W _C	W _A	M.S., pts.	C.R., pts.	P, pts.
L-3770M	2.9	91.1	1.0	0.5	27.7	14.2	41.9
T-2465M	9.7	77.4	1.0	0.5	35.5	22.5	58.0
L-3404	4.3	86.4	1.0	0.5	28.8	40.0	68.8
L-3407	21.9	89.5	1.0	1.0	81.3	7.0	88.3
L-3769M	26.1	91.1	1.0	1.0	89.1	21.8	110.9
Maximum	30.0	100.0	1.0	1.0	100.0	100.0	200.0

Figure 25. Comparison of overall performance of zinc ferrite sorbents under Criterion 3.

SECTION 6

CONCLUSIONS AND RECOMMENDATIONS

The use of zinc ferrite as a sorbent for high-temperature, moving-bed systems was evaluated at the bench-scale level. From the analysis of the results, the following conclusions can be made:

1. The use of the rounding technique for the fabrication of rounded ellipsoidal zinc ferrite pellets significantly increases the mechanical strength of the resulting pellets over that of cylindrical extrudates having the same chemical composition. Attrition resistance was increased from 88.8% for the baseline cylindrical extrudate up to 97.5% for rounded ellipsoidal pellets.
2. Binder chemical composition has a major effect on the mechanical strength and chemical reactivity of the resulting sorbent formulations by affecting the pore structure (specific pore volume and median pore diameter). After extended 10-cycle testing in the bench-scale reactor system, the binder performance can be summarized as follows:
 - The combination of calcium sulfate (10% wt/wt) and bentonite (2% wt/wt) gave the best overall performance in terms of high mechanical strength (both attrition resistance and crush strength) and acceptable chemical reactivity (single-pellet TGA and bench-scale testing) of all formulations tested in the bench-scale reactor system.
 - Bentonite alone (2-3%) imparted the porosity necessary for high chemical reactivity, but does not inhibit losses in attrition resistance and crush strength.
 - Calcium aluminate (12%)/bentonite (3% by weight) introduced added mechanical strength (both crush strength and attrition resistance) at the expense of gradual lower chemical reactivity through the extended reactor testing. This behavior was a result of the formation of calcium-sulfur compounds that added strength but decreased the specific pore volume of the pellet.
3. The performance of the five zinc ferrite formulations tested over 10 cycles of H₂S absorption and regeneration in a bench-scale reactor system indicates that chemically and mechanically durable sorbents suitable for moving-bed systems can be fabricated as ellipsoidal pellets. However, chemical reactivity and mechanical strength were found to be inversely related because denser, less porous formulations were found to be stronger and, generally, less reactive. A trade-off between these two properties is necessary in order to produce a formulation that is both chemically and mechanically acceptable. L-3769M, containing 10% calcium sulfate and 3% bentonite was found to be the formulation having the best overall balance of the two properties.
4. Sorbent reactivity in the bench-scale reactor was determined by comparing the calculated the dimensionless time at the 200 ppm H₂S breakthrough, which is related to the theoretical sulfur capacity of the sorbent and eliminates differences in binder content of the sorbents. Dimensionless times are generally defined as the ratio of real time by the time required to flow a theoretical amount of H₂S through the sorbent bed that would result in 100% sulfidation of the sorbent. The dimensionless time at the 200 ppmv breakthrough for each of the five sorbents tested in the bench-scale reactor ranged from 0.05 to 0.30 (or 5-30% of theoretical bed capacity) and followed the trend:

$$L-3407 < L-3770M < L-3769M < T-2465M < L-3404$$

This trend was explained by differences in specific pore volumes of the sorbents before and after the testing. Chemical analysis for total sulfur on sulfided pellets extracted from three locations in the bed translated into actual bed utilizations up to 37%. The measured bed utilizations correlated very well with predicted dimensionless times.

5. Measured reactor pre-breakthrough H_2S effluent concentrations, 15 ppmv or less, are satisfactory for the use of any of the laboratory-tested five sorbent formulations in commercial high-temperature desulfurization systems. These pre-breakthrough concentrations translate into approximately 99.9% sulfur removal from the simulated coal gas.
6. Reductive regeneration during bench-scale testing releases short bursts of SO_2 and H_2S up to 4000 ppmv for the first two minutes. Even though most of the sulfate formed during oxidative regeneration at 1000 °F was decomposed by the last step of oxidative regeneration (1400 °F under air for 2 hours), reductive regeneration might always be necessary. Using the GE moving-bed system, the reductive regeneration gases containing SO_2 do not represent an emission problem since they are returned to the gasifier, to the absorber, or sent to the SO_2 treatment process.
7. Sorbent formulations that maintained comparable specific pore volume, SPV, as fresh and as cycled materials, such as L-3404, also maintained their chemical reactivity through the 10 cycles of testing. Those that experienced a significant decrease in SPV, such as L-3407, did not maintain the same reactivity. Satisfactory pore volumes for zinc ferrite sorbents were in the range 0.20 to 0.30 cc/g. Smaller SPVs became more susceptible to pore plugging, incomplete regenerability, and loss of reactivity.
8. Amounts of residual carbon after bench-scale testing were always less than 0.20%. The low values are probably due to the high-steam simulated gas composition used and do not represent a problem for system operation.
9. Elemental analysis of regenerated pellets from the bench-scale reactor by SEM/EDX and SEM/EMA showed homogeneous microscopic distribution of zinc in L-3407, containing calcium aluminate binder, but segregation into microscopic clusters in L-3404, containing bentonite binder only. Distribution of Fe, Zn, and S across the pellet diameter revealed migration of zinc from the outside to the center of the pellet in both cases, more so in L-3407, presumably because of zinc vaporization followed by capillary condensation in inner smaller pores of the pellet. Hence, zinc evaporation was not a problem under the conditions tested but zinc migration may be a cause for the decrease in reactivity of L-3407.
10. Residual sulfur in the regenerated samples (i.e., sulfur remaining in the sorbent after regeneration and excluding sulfur in the binder) was always 1% wt. or less, except for L-3407 which was about 2.5%. The residual sulfur in the regenerated sorbents represents a small amount of the total sulfur during absorption, measured up to 18.8% total sulfur or 20.0 g sulfur/100 g sorbent. Sulfate sulfur was usually between 16 and 69% of the total sulfur.

The following recommendations can be made for future work:

- To further study the use of calcium-based binders and other cements in zinc ferrite sorbents; calcium-based binders (e.g., calcium aluminate and calcium sulfate) were found to increase the mechanical strength of the sorbent over multiple-cycle testing above bentonite and other binders. The key issue is to be able to control pore size within a narrow range in order to prevent pore plugging on sulfidation.

- To determine the long-term effect of other contaminants in the coal gas (e.g., tars, chloride, ammonia, alkali) on the desulfurization performance of zinc ferrite.
- To explore the use of additives to zinc ferrite for enhanced performance such as tar cracking, ammonia decomposition, and alkali removal. Metal oxides used in the petroleum refining industry could be used as starting candidates.
- To investigate the use of other mixed-metal oxides, such as zinc titanates, for desulfurization of highly-reducing gases where iron oxide has limited use. In addition, to determine the degree of metal migration or segregation as a result of temperature and/or concentration gradients within the sorbent pellets.
- To adopt a standard attrition test that incorporates weighting factors for pellet size distribution instead of the current ASTM D4058-81 where only oversize (+20 mesh) and undersize (-20 mesh) are compared.

REFERENCES

- Ayala, R.E., and B.M. Kim. 1989. "Modeling and Analysis of Moving-Bed Hot-Gas Desulfurization Processes." *Environ. Prog.* 8:19-25.
- Ayala, R.E., E. Gal, S.K. Gangwal, and S.C. Jain. 1990. Enhanced Durability of High-Temperature Desulfurization Sorbents for Moving-Bed Applications. In *Proc. American Chemical Society Div. Fuel Chemistry* 35(1): 120-127.
- Ayala, R.E., and D.W. Marsh. 1991. "Characterization and Long-Range Reactivity of Zinc Ferrite in High-Temperature Desulfurization Processes." *Ind. Eng. Chem. Res.* 30:55-60.
- Cook, C.S., B. Parekh, R.M. Tucker, E. Gal, and A.H. Furman. 1989. Integrated Operation of a Pressurized Fixed-Bed Gasifier and Hot Gas Desulfurization System. In *Proceedings of the Ninth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, p. 37-46. DOE/METC-89/6107. NTIS/DE89011706.
- Corman, J.C. 1986. "System Analysis of Simplified IGCC Plants," Topical Report. U.S. Dept. of Energy, DOE/ET/14928-2233.
- Flytzani-Stephanopoulos, M., S. Lew, and A.F. Sarofim. 1990. "Hot Gas Desulfurization by Zinc Oxide-Titanium Dioxide Regenerable Sorbents." In *Proc. American Chemical Society Div. Fuel Chemistry* 35(1): 77-86.
- Gangwal, S.K. 1990. Enhanced Durability of Desulfurization Sorbents for Fluidized-Bed Applications. In *Proceedings of the Tenth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, Vol 1. p. 102-111. DOE/METC-90/6115. NTIS/DE90009689.
- Gangwal, S.K.; S.M. Stogner, and S.M. Harkins. 1989a. "Testing of Novel Sorbents for H₂S Removal from Coal Gas." *Environ. Prog.*, 8:26-34.
- Gangwal, S.K., S.M. Harkins, M.C. Woods, S.C. Jain, and S.J. Bossart. 1989b. Bench-Scale Testing of High-Temperature Desulfurization Sorbents. *Environmental Progress* 8(4): 265-269.
- Grindley, T., and G. Steinfeld. 1985. Desulfurization of Hot Coal Gas by Zinc Ferrite. *Acid and Sour Gas Treatment Proc.*, Gulf Publishing Co., Houston, Texas, pp 419-465. Also Grindley, T., S.S. Kim, E.E. Gorski, and G. Steinfeld. 1985. "Aspects of the Design of a Process Development Unit for High-Temperature Coal Gas Desulfurization," *Proceedings. Fifth Annual Contractor's Meeting on Contaminant Control in Hot Coal-Derived Gas Streams*, U.S. Dept. of Energy/METC, Morgantown, WV, p. 33-62. DOE/METC-85/6025.
- Haldipur, G.B., K.J. Smith, S. Datta, and P. Cherish. 1988. "Fluidized Bed Coal Gasification with Hot Gas Cleanup," in *Proceedings of the Eighth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, V.P. Kothari and J.R. Longanbach (Editors), Morgantown Energy Technology Center, Morgantown, West Virginia, pp 32-44. DOE/METC-88/6092 (DE88010253).

Jain, S.C., S.K. Gangwal, E. Gal, and R.E. Ayala. 1990. A Study of the Chemical Reactivity and Mechanical Durability of High-Temperature Desulfurization Sorbents for Moving-Bed and Fluidized-Bed Applications. Paper 76f, 1990 AIChE National Meeting, San Diego, California, August 19-22.

Jalan, V.M. Desai, and F. Brown, 1989. Copper-Based Sorbents for Hot Gas Cleanup. In *Proceedings of the Ninth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, p. 541-547. DOE/METC-89/6107. NTIS/DE89011706.

Jha, M.C., M.H. Berggren, and D.P. Harrison. 1989. Enhanced Durability and Reactivity for Zinc Ferrite Desulfurization Sorbent. In *Proceedings of the Ninth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, p. 96-105. DOE/METC-89/6107. NTIS/DE89011706.

Koch, R.W. 1989. Technical and Economic Comparison of Gas Desulfurization Processes. In *Proceedings of the Ninth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, Vol. 2, pp. 620-631. DOE/METC-89/6107. DE89011707.

Kolta, G.A.; S.W. El-Tawil, A.A. Ibrahim, and N.S. Felix. 1980. "Kinetics and Mechanism of Zinc Ferrite Formation." *Thermochim. Acta*, 36:359-366.

Krishnan, G.N.; G.T. Tong, R.H. Lamoreaux, and R.D. Brittain. 1985 Wood, B.J. A Study of Sulfate Formation During Regeneration of Zinc Ferrite Sorbents. In *Proceedings Fifth Annual Contractors' Meeting on Contaminant Control in Coal-Derived Gas Streams*, U.S. Dept. of Energy/METC, Morgantown, WV. p. 6-18. DOE/METC-85/6025.

Smith, D.P., E. Gal, C.S. Cook, and A.H. Furman. 1987. Design Studies for Hot Gas Cleanup System in a Load Following Mode. In *Proceedings of the Seventh Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, p. 678-692. DOE/METC-87/6079. NTIS/DE87006496.

Sugitani, T. 1987. "Fundamental Studies and Present Status of IHI Hot Gas Desulfurization Process." *Intl. Conf. Coal Sci.* J.A. Moulgyn et al., (eds.) Elsevier Science Publishers B.V., Amsterdam, pp. 915-919.

Torres-Ordoñez, R.J., J.P. Longwell, and A.F. Sarofim, 1989. Intrinsic Kinetics of CaS(s) Oxidation. *Energy Fuels* 3:506-515.

Woods, M.C., K.E. Leese, S.K. Gangwal, D.P. Harrison, and K. Jothimurugesan, 1989. Reaction Kinetics and Simulation Models for Novel High-Temperature Desulfurization Sorbents. Final report DOE/MC/24160-2671. NTIS/DE89000950.

Wu, J.C., A.M. Robin, and J.S. Kassman. 1989. "Integration and Testing of Hot Desulfurization and Entrained Flow Gasification for Power Generation Systems" in *Proceedings of the Ninth Annual Gasification and Gas Stream Cleanup Systems Contractors Review Meeting*, Vol. 1, pp. 25-36. DOE/METC-89/6107. DE89011706.

**DATE
FILMED**

5 / 29 / 92