2.

Characterization of Multiphase Fluid Flow During Air-Sparged Hydrocyclone Flotation by X-Ray CT

DOE/PC/90311--10

DE93 012471

Tenth Quarterly Report
14 November - 13 February

DOE Contract No. DE-FG22-90PC90311

Submitted by :

J.D. Miller
Professor of Metallurgical Engineering
216 WBB
University of Utah
Salt Lake City, Utah 84112
(801)-581-5160

March 1, 1993

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

REPORT FOR TENTH QUARTER
14 November -- 13 February

During this quarter of the DOE project, "Characterization of Multiphase Fluid Flow During Air-sparged Hydrocyclone Flotation", a new set of experiments was carried out with and without collector in order to understand the flow patterns inside the ASH unit for both hydrophilic and hydrophobic particles. These tests were designed to study the effects of percent solids in the feed, A^* - the nondimensional ratio of overflow opening area to underflow opening area, and the effect of collector addition on the flow characteristics. These experiments were done with 0%, 5% and 15% solids in the feed. The latter two cases were studied for three different A^* values and also with and without the addition of collector. The value of Q^* , the dimensionless ratio of air flow rate and slurry flow rate was maintained at the same level ($Q^* = 4.55$).

Quartz particles of size -100 +200 mesh were used for this study rather than coal particles because they did not abrade and were of a higher density. The reagents and their dosages used were 40 ppm (water basis) of frother (MIBC) and 800 g of collector (dodecyl amine) per ton of solids in the suspension. At room temperature, quartz is intrinsically hydrophilic while addition of the amine collector renders the quartz particles hydrophobic. The absence of collector will be referred to as the hydrophilic case and the presence of collector will be referred to as the hydrophobic case.

A total of 11 scans was taken over the entire length of the

ASH unit. Software has now been developed to analyze the CT images obtained from these tests and is able to account for any offset of the air core from the axis of the ASH. In this way, the image is reconstructed and a radial density profile of the time averaged flow is generated. Some experimental results are presented graphically in Figures 1 through 4 at 0% and 5% solids in the suspension for both hydrophilic and hydrophobic cases.

Figure 1 shows the density profiles at the top, middle and bottom of the ASH without any solids in the feed slurry. The air core diameter (zero density region) remains the same throughout the length of the ASH. The froth region is narrow at the top and absent elsewhere while the swirl layer region stabilizes at a constant thickness as one goes down the axis of the ASH. These data serve as a point of reference for comparison.

Figure 2 shows the radial density profiles for 5% solids in the suspension and $A^* = 1.00$ with and without collector addition. In the hydrophobic case the air core is larger when compared to the hydrophilic case and decreases in size at lower levels in the ASH. The swirl layer is very thin at the top and wide at the bottom. The froth seems to be unstable at such low percent solids in the feed slurry and such a high value of A^* ($A^* = 1.00$).

It can be seen from Figure 3 that as the value of A^* is reduced from 1.00 to 0.85, the air core expands for both hydrophilic and hydrophobic cases. The froth stability is higher at this A^* value and a clear froth region could be noticed at the bottom of the ASH in the hydrophobic case. However, there is no noticable change for the hydrophilic case.

Investigation of Figure 4 reveals that as the A^* value is further reduced to 0.74, the air core expands again for both hydrophilic and hydrophobic cases. The swirl layer does not change much along the axis but the air core shrinks and the froth region expands at lower levels in the ASH unit.

Comparison of Figure 2, 3 and 4 reveals that the air core expands with an increase in the value of A^* . The distribution of air is unequal along the length of the ASH; more air flows through the bottom than through the top. This is because the centrifugal force field is very strong at the top and because of the swirl flow decay the tangential velocity and the centrifugal force is reduced significantly at the bottom. Thus the swirl layer is in a more compressed state at the top and hence thin. Whereas, the swirl layer is under a lower pressure at the bottom and hence thicker. From the density gradients observed it appears that the froth is more stable in hydrophobic case and at lower A^* values. The air core for the hydrophobic case is almost always larger than the air core for the corresponding hydrophilic case.

It should be mentioned that a certain amount of error is introduced while reconstructing the CT images. This makes it difficult to unambiguously distinguish between adjacent flow regimes, eg. the froth region and the swirl region. For example, the resolution is expected to be accurate to ± 2 mm. Efforts are being made to quantify this error and account for it. The experimental results with 15% solids in the suspension and different A^* values for hydrophilic and hydrophobic cases will be reported in the next quarterly report.

Figure 1 : Radial density profile at the top, middle and bottom of the ASH for 0% solids and $A^* = 1.00$

Figure 2 : Radial density profile at the top, middle and bottom of the ASH for 5% solids and $A^* = 1.00$

Figure 3 : Radial density profile at the top, middle and bottom of the ASH for 5% solids and $A^* = 0.85$

Figure 4 : Radial density profile at the top, middle and bottom of the ASH for 5% solids and $A^* = 0.74$

END

DATE
FILMED

5 / 20 / 93