DOE/ER/45365--5

DE93 008636

TRANSFORMATION PLASTICITY IN DUCTILE SOLIDS

Annual Progress Report
for the Period June 1, 1992 - May 31, 1993

G. B. Olson
Northwestern University
Evanston, Illinois 60208

February, 1993

Prepared for
THE U.S. DEPARTMENT OF ENERGY
AGREEMENT NO. DE-FG02-88ER45365

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

for

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

Abstract

Research has addressed the role of martensitic transformation plasticity in the enhancement of toughness in high-strength austenitic steels, and the enhancement of formability in multiphase low-alloy sheet steels. In the austenitic steels, optimal processing conditions have been established to achieve a significant increase in strength level, in order to investigate the interaction of strain-induced transformation with the microvoid nucleation and shear localization mechanisms operating at ultrahigh strength levels. The stress-state dependence of transformation and fracture mechanisms has been investigated in model alloys, comparing behavior in uniaxial tension and blunt-notch tension specimens. A numerical constitutive model for transformation plasticity has been reformulated to allow a more thorough analysis of transformation/fracture interactions. Processing of a new low alloy steel composition has been optimized to stabilize retained austenite by isothermal bainitic transformation after intercritical annealing. Preliminary results show a good correlation of uniform ductility with the austenite amount and stability.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Progress Report

Personnel involved in our program in the subject period have included Professor G. B. Olson as Principal Investigator committing 8.3% calendar year, Research Assistant Professor Gautam Ghosh performing transformation kinetic modelling, Research Assistant David Bergstrom studying transformation plasticity in austenitic steels, Graduate Fellow Mitch Brandt studying transformation plasticity in multiphase low alloy steels, Senior Project Student Scott Pope studying metastable cobalt alloys, and Administrative Assistant James Herman. Collaborative work at MIT under subcontract has involved Professor D. M. Parks as Principal Investigator and Research Assistant Simona Socrate performing finite-element modelling of transformation plasticity behavior.

David Bergstrom has continued study of transformation toughening in a series of model austenitic alloys previously investigated in the doctoral research of Frode Stavehaug. In order to examine transformation interactions with the failure mechanisms operating at ultrahigh strength levels, the thermochemical treatment has been increased from a 40% to a 70% reduction at 450C, and aging treatment at 650-700C has been optimized, monitoring hardness and tensile properties. A 12.5% strength increase has been achieved, corresponding to a yield strength of 200-230 ksi, with good fracture ductility. In another model alloy previously investigated in the doctoral research of Chune-Ching Young, fracture strains and transformation characteristic M_s^0 temperatures have been evaluated in blunt-notch and uniaxial tensile specimens to define model parameters governing the stress-state dependence of both transformation kinetics and microvoid nucleation behavior.

Toward the development of a comprehensive kinetic model for predictive control of mechanically induced transformation behavior as a function of alloy composition and strength level, Professor Ghosh has evaluated solution hardening coefficients governing martensitic interfacial mobility in multicomponent ferrous alloys. The resulting model for the composition dependence of the critical thermodynamic driving force for martensitic nucleation was presented at the International Conference on Martensitic Transformations (ICOMAT-92) in Monterey, CA in July 1992. Extrapolating model parameters to Co-base alloys, a prototype transformation-toughened Co-Cr-Fe alloy of potential interest for biomedical applications was designed in an undergraduate materials design class. The alloy has been prepared by Republic Steel, and is being evaluated by undergraduate student Scott Pope as a Senior Project.

The transformation plasticity constitutive model developed in the previous doctoral research of Richard Stringfellow has been published in Acta Metallurgica. To obtain a more robust numerical implementation suitable for simulation of fracture processes, the model has been reformulated by Simona Socrate working with Professor Parks. The number of internal state variables has been reduced, the number of nonlinear equations has been decreased from eight to four, and a two-level solution procedure has been devised where only the outer level, consisting of a single equation, is strongly nonlinear. The model has been demonstrated to be well behaved in load-unload cycles similar to events accompanying local fracture processes.

Toward enhancement of formability in multiphase low alloy steels, Mitch Brandt has investigated a new steel composition prepared by Inland Steel. To vary retained austenite stability and amount in ferrite/bainite/austenite microstructures, specimens intercritically annealed at 775C have been partially bainitically transformed at 350-400C for varying reaction times. Austenite amount and carbon content have been monitored by Xray diffraction, and the M_s^σ temperature defining austenite stability has been determined from the measured temperature dependence of yield stress. Uniform ductility in uniaxial and plane-strain tension have been correlated with the austenite stability and amount. At a 3% flow strength of 90 ksi, a uniform ductility of 45% can be obtained at optimum austenite stability at a volume fraction of 16%. Preliminary results were presented at the G R. Speich Symposium of ISS/AIME in Montreal, October 1992, and have been published in the proceedings.

Invited lectures presenting results from this research program were also given by Prof. Olson at the following locations:

Cambridge University	April 23, 1992
Oxford University	April 30, 1992
University of Surrey	May 15, 1992
Royal Institute of Technology, Stockholm	May 20, 1992
Stocksbridge Engineering Steels, Sheffield	June 15, 1992
Intl. Conference on Martensitic Transformations, Monterey, CA	July 24, 1992
S & C Electric, Chicago	July 30, 1992
NUTEK/NFR European Materials Research Consortia Symposium	October 8, 1992
Third Intl. Stein Conference: Advanced Materials, Philadelphia, PA	October 20, 1992
ASM/SAE Chapter, Peoria IL	November 9, 1992
ASM/SAE Chapter, Decatur IL	November 10, 1992
IIT Materials Colloquium	November 12, 1992
Gillette Company, Boston MA	December 3, 1992

Recent Publications Stemming from this Grant

R. G. Stringfellow, D. M. Parks, and G. B. Olson, "A Constitutive Model for Transformation Plasticity Accompanying Strain-Induced Martensitic Transformations in Metastable Austenitic Steels," Acta Metall. Mater. Vol. 40, No. 7, (1992) pp. 1703-1716.

M. L. Brandt and G. B. Olson, "Bainitic Stabilization of Austenite in Low Alloy Steels," Proc. Gilbert R. Speich Symposium: Fundamentals of Aging and Tempering in Bainitic and Martensitic Steel Products," eds. G. Krauss and P. E. Repas, ISS-AIME, Warrendale PA, (1992) pp. 257-265.

G. Ghosh and G. B. Olson, "Solid Solution Strengthening and Kinetics of Martensitic Transformations in Fe-Base Alloys," Proc. ICOMAT-92, ed. J. Perkins, in press.

G. B. Olson, "Mechanically Induced Phase Transformations in Solids: An Update," Encyclopedia of Materials Science and Engineering, Pergamon, in press.

END

**DATE
FILMED**

4 / 30 / 93