THE UNIVERSITY OF NEW MEXICO
SCHOOL OF MEDICINE

ALBUQUERQUE, NEW MEXICO 87131

April 17, 1989

RECEIVED
APR 22 1994
OSTI

Robert E. Hermes, Ph.D.
Polymers and Coatings Group, MST-7
Los Alamos National Laboratory
Los Alamos, New Mexico 87545

Dear Robert,

We have now completed studies on the adsorption of radiolabeled thrombin and fibrinogen to the second batch of polymers you have provided for this purpose. The proteins are of human origin, and were freshly labeled for this study. As before, the thrombin was active-site blocked by reaction with diisopropylfluorophosphate to prevent autolysis. The thrombin was labeled with iodine-125 and fibrinogen with iodine-131, and since the former had no enzymatic activity the two labeled proteins were added together to the polymer cups. Thus, these data represent the results of a single experiment done in triplicate, in which the adsorption of ^{125}I -thrombin and ^{131}I -fibrinogen were analyzed simultaneously.

As I mentioned to you when we talked last week, I think the thrombin results are very interesting. For the first 80 min after addition of the ^{125}I -thrombin, a minimal amount of this protein was adsorbed by any of the new polymer materials. In contrast, polystyrene and old tecoflex cups adsorbed the labeled protein throughout the course of the experiment. Reflecting these results, we found that after washing the polystyrene and the old tecoflex had adsorbed 3-4 and 2-2.5 times more ^{125}I -thrombin respectively than the new polymers.

The fibrinogen data seem to be less interesting, as adsorption by all polymers was fairly constant throughout the period of the experiment. These results were again reflected in the results of the counting of the polymer cups after washing.

After you, Bruce Lehnert and the others there have had chance to consider these data, I would be most interested in discussing it with you further.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Sincerely,

Tim

Timothy H. Carlson, Ph.D.
Research Asst. Professor

Time (min)	Polystyrene	New TF	Ty	Tx	Tz	Old TF
*I-Thrombin Remaining in 20 ul Solution (+ 1 S.D.) (131698±4452 counts/20 ul/well added at t = 0)						
0	127647 ±7497	126696 ±1627	120618 ±2124	122657 ±3454	121134 ±2217	109680 ±4179
10	93756 ±5268	116139 ±304	119659 ±3089	117842 ±3321	111041 ±9046	96635 ±7766
20	73520 ±8876	110038 ±1502	120150 ±1054	119612 ±5311	116367 ±3815	87022 ±4053
40	63590 ±2568	111958 ±1472	118522 ±6618	118079 ±4484	116875 ±3021	72714 ±3848
80	50793 ±7173	113689 ±1928	121049 ±930	117298 ±3326	115776 ±4306	65140 ±1643
160	43221 ±9978	102303 ±6003	108688 ±4309	107693 ±1382	104302 ±3901	56306 ±4921
320	33567 ±6719	84071 ±3599	96245 ±1305	92634 ±4898	77106 ±23343	51789 ±4013

*I-Thrombin Bound to the Cups after Washing

875199 ±42658	262244 ±45845	216795 ±2446	243939 ±8564	260136 ±30526	514983 ±28303
------------------	------------------	-----------------	-----------------	------------------	------------------

n=3

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Time (min)	Polystyrene	New TF	Ty	Tx	Tz	Old TF
---------------	-------------	-----------	----	----	----	-----------

*I-Fibrinogen Remaining in 20 ul Solution (+ 1 S.D.)
(102607+3225 counts/20 ul/well added at t = 0)

0	98948 ±1132	98596 +3739	94234 ±1085	97832 ±2788	96302 ±2282	95300 ±2287
10	88842 ±2032	92886 ±1333	89100 ±2201	88588 ±1921	86920 ±2610	88640 ±2726
20	75424 ±4495	77858 ±1819	82529 ±4400	79621 ±1748	78590 ±2872	80638 ±1889
40	62833 ±3752	73472 ±994	73684 ±4472	69751 ±2662	67858 ±2048	68366 ±3551
80	39667 ±4440	57577 ±6206	54366 ±2564	50049 ±2671	51875 ±2154	51702 ±573
160	20148 ±2172	37056 ±7459	30105 ±2121	29073 ±2047	33809 ±5284	27534 ±5055
320	14133 ±1711	26211 ±3013	15682 ±1570	14831 ±931	16250 ±4011	18648 ±1306

*I-Fibrinogen Bound to the Cups after Washing

701031	534300	609196	643473	657753	593397
±14801	±65148	±24916	±3302	±33826	±1307

n=3

FINAL REPORT .

Studies on the Interaction of Blood Components with Ultra-Smooth Polymer Surfaces

Part B: Evaluation of Neutrophil Adherence and Activation

PURPOSE

The purpose of this part of the study was to evaluate the adherence of human neutrophils (PMN) to various polymeric membrane surfaces.

PROCEDURES

PMN were prepared from heparinized blood by Ficoll-Hypaque density gradient centrifugation. The cell pellet containing PMN was resuspended to the original blood volume in Hank's balanced salt solution (HBSS). Plasmagel was added to the suspension (1 ml of Plasmagel to 1 ml cell suspension) and erythrocytes were allowed to sediment for 30 minutes at 20°C. The PMN-rich supernatant was then aspirated and centrifuged at 300xg for 10 minutes. Residual contaminating erythrocytes were lysed with a 30-second, 4°C., distilled water treatment. This cell preparation was then centrifuged again and the cells were washed with HBSS and suspended to 1×10^6 cells/ml of RPMI or various serum concentrations as described below.

Initially each disc (nonhydrated) was evaluated in duplicate using PMN from 3 different donors. The discs were put in the bottom of the chamber, the sleeves added, and the screw caps hand-tightened. 1.5 ml of cells ($10^6/\text{ml}$) were added to each chamber. The chambers were then incubated at 37°C, for 30 minutes. Then the chambers were oscillated in a shaking water bath for 30 seconds.

The supernatant and floating cells were aspirated off and then the discs were gently washed 3 times with RPMI. The discs were air-dried and the adherent cells were quantitated using an Artek automated video counting system using a 10x objective on a light microscope. The number of PMN per mm^2 were determined by counting 20 fields per disc.

The data are presented in Tables 1, 2, and 3 and Figures 1-4. The results indicate that there is considerable variation from donor to donor. The overall means indicate that the discs having the least adherence (in order) were 6 (Tecoflex treated with PEG 30%), 2 (Tecoflex grafted with HEMA), and 9 (Tecoflex infused with PVP/Iodine). The treated discs with the most adherence were 1 (Tecoflex grafted with NVP) and 3 (Tecoflex grafted with PVP 5%).

Following this set of experiments, we compared the effect of hydrating the discs. The discs were hydrated for 24 hours in glass-distilled water and then air-dried. The discs tested were those that had shown to be the least adherent in the previous experiments. The data comparing nonhydrated and hydrated discs are presented in Figure 5 and Table 4. These results indicate that hydration of the discs did not significantly decrease their adherent properties.

The next step considered the effect of resuspending PMN in serum and then testing the discs for adherence. Polystyrene discs were tested in duplicate using different concentrations of serum (Table 5 and Figure 6). Based on this experiment we then compared the adherence of PMN suspended in RPMI and PMN suspended in 30% serum using 8 different discs (Table 6 and Figure 7). These results indicate that PMN suspended in 30% serum were significantly more adherent than PMN in RPMI.

Table 1
Comparison of Nonhydrated Discs

	1A	2A	3	4	5	6	7	8	9	10	11	TECO1	POLY2	TECO2	POLY1
9-1-88 A *	357.1	194.3	342.6	351.5	393.7	256.2	301.3	207.1	257	391.6	363.1	435.3	458.1	368.8	256.6
B	365.1	126.2	265.1	388.7	346.7	265.3	273.3	294.7	273.3	389.2	380	374.4	409.3	459.7	436.3
9-6-88 A	230.2	206.1	233.4	190.6	170.8	137.1	246.3	209.2	188.7	190.2	174.4	200.3	262.9	308.5	373
B	216.7	208.3	227	191.2	221.6	147.3	224.6	171.1	167.3	210	184.3	192.2	258.5	291.6	353.2
9-7-88 A	293.4	294.1	310.5	252.7	257.2	217.5	317.3	394.1	255.5	289.6	291.7	232.2	302.1	414.1	421.3
B	265	256.6	344	251.3	229.7	218.6	240.3	395.9	219.7	224	265.3	422.1	406.3	430.1	483.6
TOTAL MEAN	287.9	214.3	287.1	271	270	207	267.2	278.7	226.9	282.4	276.5	309.4	349.5	378.8	387.3
SD	57.3	52.32	48.04	75.1	76.5	49.18	33.4	90.2	38.6	82.2	79	103.6	78.12	62	72.2

* A and B are duplicate runs of the same disc

Figure 1

COMPARISON OF DISCS

Values are mean of 3 runs

T=tectoflex
P=polystyrene

Table 2

Comparison of Nonhydrated Discs in 3 Different Runs

	RUN1	RUN2	RUN3	OVERALL MEAN
TECO1	404.8	196.2	427.1	342.7
TECO2	414.2	300.1	422.1	378.8
POLY1	339.3	363.1	354.2	384.9
POLY2	433.7	260.7	452.4	349.5
1	361.1	223.4	279.2	287.9
2	160.2	207.2	275.3	214.2
3	303.2	230.2	327.2	287.1
4	370.1	190.9	252	271
5	370.2	196.2	243.4	269.9
6	260.7	142.2	218.1	207
7	287.3	235.4	278.8	267.2
8	250.9	190.1	395	239.9
9	265.1	178	237.6	226.9
10	390.4	200.1	256.8	282.4
11	371.5	179.3	278.5	276.4

SORTED DATA BY	Overall MEANS
POLY1	384.9
TECO1	378.8
POLY2	349.5
TECO2	342.7
1	287.9
3	287.1
10	282.4
11	276.4
4	271
5	269.9
7	267.2
8	239.9
9	226.9
2	214.2
6	207

Table 3

Sorted Data by Means for Each Run

	RUN#1
polystyr2	433.7
tecoflex2	414.2
tecoflex1	404.8
10	390.4
11	371.5
5	370.2
4	370.1
1	361.1
polystyr1	339.3
3	303.8
7	287.3
9	265.1
6	260.7
8	250.9
2	160.2

	RUN#2
polystyr1	363.1
teco2	300.1
polysty2	260.7
7	235.4
3	230.2
1	223.4
2	207.2
10	200.1
5	196.2
teco1	196.2
4	190.9
8	190.1
11	179.3
9	178
6	142.2

	RUN#3
poly2	452.4
teco#1	427.1
teco#2	422.1
8	395
poly1	354.2
3	327.2
1	279.2
7	278.8
11	278.5
2	275.3
10	256.8
4	252
5	243.4
9	237.6
6	218.1

Figure 2

COMPARISON OF DISCS RUN #1

Figure 3

COMPARISON OF DISCS RUN #2

Figure 4

COMPARISON OF DISCS RUN #3

COMPARISON OF HYDRATED AND NONHYDRATED DISCS

Figure 5

Table 4

Comparison of Hydrated and Nonhydrated Discs

		NOWATER		WATER	
		MEAN	SD	MEAN	SD
TECO		276.4	51.1	335	34.7
POLY		368.8	61.7	251	50
	6	261.6	41.9	220.5	71.1
	2	208.9	56.3	227.7	56.1
	8	306.6	76.4	339.8	76.6
	7	268.6	54.5	200.6	50.5
	5	182.1	34.5	174.4	44.4
	9	275.1	54.5	281	58.8

Table 5

Comparison of Different Concentrations of Serum
Using Polystyrene Discs

	DISC A *		DISC B		OVERALL MEAN	
	mean	sd	mean	sd	mean	sd
FFMI	309.5	23.84	279.7	21.58	294.7	21.07
10 % serum	364	67.66	290.7	78.47	327.3	51.83
20% serum	359.3	69.68	310.1	47.61	334.7	34.79
30%serum	316.6	45.51	311.2	41.13	313.9	3.81
40% serum	275.3	33.49	296.1	55.45	285.7	14.71
50% serum	267.3	38.97	263.4	44.99	265.35	2.76
100% serum	241.7	22.35	329.7	26.24	285.7	62.22

*Disc A and B are duplicate discs

Figure 6

COMPARISON OF ADHERENCE OF PMN TO POLYSTYRENE DISCS USING DIFFERENT CONCENTRATIONS OF SERUM

Table 6

Comparison of RPMI and 30% Serum on Adherence of PMN

	RPMI		30% SERUM	
	MEAN	SD	MEAN	SD
TECO	205.5	51.43	338.4	76.71
POLY	309.4	50.59	305.4	62.77
9	41.4	16.75	204.9	57.41
11	43.7	21.64	225.4	39.89
10	61.8	26.63	87.6	28.37
7	89.1	32.09	225.6	50.25
4	34.4	27.71	182.2	51.24
1	61.4	34.29	148	93.09

Figure 7

COMPARISON OF ADHERENCE OF PMN USING RPMI OR 30% SERUM

SCHOOL OF MEDICINE
DEPARTMENT OF MEDICINE
Albuquerque, NM 87131

PART C

September 6, 1988

Debra Wroblewski, Ph.D.
Mail Stop E-549
Los Alamos National Laboratories
Los Alamos, NM 87545

Dear Debra:

I am sending a summary of the initial studies on the Tecoflex and treated Tecoflex cups that I told you about. The assay basically incubated three different normal serum samples with wells in duplicate for 30 min at 37°. Then I used an enzyme-linked antibody to measure C3 bound to the wells. The controls are Tecoflex at 4° which showed little C3 binding. I also blocked complement activation with MgEGTA or EDTA (chelators). This showed that the C3 binding to the Tecoflex was due to classical pathway activation. The treated surfaces in general showed increased C3 binding compared to Tecoflex. There was a big difference between donors in a few of the surfaces, but the overall results were fairly consistent. I will try hydrated surfaces by this assay and I have all the serum from these experiments to test for complement split products.

Sincerely,

Carolyn Mold

C3 Binding to modified Tecoflex

SAMPLE	CM 826a	CM 826b	CM 826x	KG 829a	KG 829b	KG 829x	ED 901a	ED 901b	ED 901x	MEAN	STDEV
1 NVP	0.414	0.546	0.480	0.680	0.288	0.484	0.292	0.538	0.415	0.460	0.156
2 HEMA	0.414	0.630	0.522	0.372	0.402	0.387	0.372	1.027	0.700	0.536	0.259
3 5%PVP	0.639	0.698	0.669	0.543	0.862	0.703	0.658	0.473	0.566	0.646	0.134
4 30%PVP	1.011	0.498	0.754	1.072	0.580	0.826	0.483	0.479	0.481	0.687	0.278
5 5%PEG	0.373	0.367	0.370	0.572	0.408	0.490	0.200	0.168	0.184	0.348	0.148
6 30%PEG	0.714	0.417	0.566	0.787	0.428	0.608	0.717	0.494	0.606	0.593	0.165
7 NVP/NaAMPS	0.322	0.406	0.364	0.139	0.280	0.210	0.226	0.143	0.185	0.253	0.105
8 HEMA/AMPS	0.605	0.570	0.588	0.246	0.367	0.307	0.542	0.695	0.619	0.504	0.166
9 PVP/Iodine	1.500	0.919	1.210	0.734	0.914	0.824	0.439	1.041	0.740	0.925	0.351
10 PVP/AgNO3	0.695	1.077	0.886	0.568	0.731	0.650	0.303	0.477	0.390	0.642	0.264
11 NVP/NaVS	0.546	0.687	0.617	0.117	0.080	0.099	0.339	0.538	0.439	0.385	0.248
Tecoflex	0.219	0.204	0.212	0.189	0.149	0.169	0.073	0.084	0.079	0.153	0.062
polystyrene	0.406	0.307	0.357	0.220	0.252	0.236	0.073	0.071	0.072	0.222	0.132
Tecoflex cold	0.045	0.119	0.082	0.146	0.190	0.168	0.089	0.062	0.076	0.109	0.054
Tecoflex MgEGTA	0.089	0.049	0.059								

All data on non-hydrated cups.

MEAN and Standard Deviation of three donors, duplicate cups.

C3 Binding to modified Tecoflex

SAMPLE	CM 826x	KG 829x	ED 901x	MEAN	CM 912xh
1 NVP	0.480	0.484	0.415	0.460	0.939
2 HEMA	0.522	0.387	0.700	0.536	0.790
3 5%PVP	0.669	0.703	0.566	0.646	1.136
4 30%PVP	0.754	0.826	0.481	0.687	0.675
5 5%PEG	0.370	0.490	0.184	0.348	0.534
6 30%PEG	0.566	0.608	0.606	0.593	0.581
7 NVP/NaAMPS	0.364	0.210	0.185	0.253	0.196
8 HEMA/AMPS	0.588	0.307	0.619	0.504	1.045
9 PVP/Iodine	1.210	0.824	0.740	0.925	0.515
10 PVP/AgNO3	0.886	0.650	0.390	0.642	0.665
11 NVP/NaVS	0.617	0.099	0.439	0.385	1.169
Tecoflex	0.212	0.169	0.079	0.153	0.345
polystyrene	0.357	0.236	0.072	0.222	0.207
Tecoflex cold	0.082	0.168	0.076	0.109	0.069
Tecoflex. MgEGTA	0.059				

Individual and overall means.

CM 912xh used hydrated cups, CM serum.

C3 Binding to modified Tecoflex

Tecoflex cold	0.109
Tecoflex	0.153
polystyrene	0.222
7 NVP/NaAMPS	0.253
5 5%PEG	0.348
11 NVP/NaVS	0.385
1 NVP	0.460
8 HEMA/AMPS	0.504
2 HEMA	0.536
6 30%PEG	0.593
10 PVP/AgNO ₃	0.642
3 5%PVP	0.646
4 30%PVP	0.687
9 PVP/Iodine	0.925

Data sorted by MEAN of three experiments.

Tecoflex C3a x

	CM	KG	ED	ng/ml C3a	CM hydrated		
	A	B	C	D	E	F	G
1	SAMPLE	0826x	0829x	0901x	MEAN	STD DEV	0912x
2	1	111.5	356.8	216.1	228.1	123.1	219.4
3	2	159.2	273.8	271.7	234.9	65.5	181.9
4	3	134.7	286.3	74.4	165.1	109.2	239.6
5	4	175.4	326.7	236.1	246.1	76.1	194.8
6	5	129.6	297.2	283.2	236.7	93.0	141.1
7	6	162.1	368.2	244.4	258.2	103.7	189.2
8	7	101.3	297.2	224.5	207.6	99.0	168.2
9	8	171.2	336.4	300.7	269.4	86.9	139.4
10	9	181.9	372.9	232.9	262.5	98.9	186.6
11	10	153.8	317.9	201.1	224.2	84.4	242.9
12	11	142.9	240.4	286.9	223.4	73.5	170.1
13	12	265.4	282.7	251.5	266.5	15.7	151.3
14	13	178.6	280.3	225.7	228.2	50.9	246.6
15	14	143.4	120.6	137.3	133.7	11.8	182.3
16	15	201.9			201.9		

= Tecoflex (37)
 = polystyrene
 = Tecoflex (cold)
 = Tecoflex (serum chelated)

The lowest value was the cold Tecoflex control. The highest was polymer #9 which was also the highest in the binding assay. The others do not correspond exactly, but there is not very much difference between the samples.

012689 C3 Binding

	A405	MEAN	SEM	
Old Tecoflex 4°	0.013			
	0.013	0.020	0.007	
	0.035			
Old Tecoflex 37°	0.195			
	0.279	0.243	0.025	
	0.254			
New Tecoflex 37°	0.522			
	0.391	0.481	0.045	
	0.531			
PVP-Tecoflex 37°	0.687			
	0.378*	0.716	0.029	
	0.745			
10%DT/PVP-Tecoflex 37°	0.514			
	0.522	0.528	0.011	
	0.549			
15%DT/PVP-Tecoflex 37°	0.487			
	0.671	0.518	0.081	
	0.397			
*excluded				

012689 C3 Binding
 normal human serum (CM)

12

need to be

DATE

FILMED

5/10/94

END