MATERIALS COMPATIBILITY AND LUBRICANTS RESEARCH ON CFC-REFRIGERANT SUBSTITUTES

Miscibility of Lubricants with Refrigerants

Quarterly Report

6 February 1992 - 31 March 1992

Michael B. Pate
Steve Zoz
Lyle Berkenbosch

Iowa State University
of Science and Technology
Department of Mechanical Engineering
2025 Black Engineering Bldg.
Ames, Iowa 50011

April 1992

Prepared for
The Air-Conditioning and Refrigeration Technology Institute

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.94% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.06% of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

The U.S. Department of Energy and the air-conditioning industry support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. neither the United States nor the Department of Energy, nor the Air Conditioning and Refrigeration Technology Institute, nor any of their employees, nor of any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

MATERIALS COMPATIBILITY AND LUBRICANT RESEARCH ON CFC-REFRIGERANT SUBSTITUTES

ABSTRACT

During this reporting period, modifications were made to the experimental apparatus in preparation for performing the experiments required in this project. In addition, new procedures for charging the lubricant and refrigerant into the cells for high temperature tests have been adopted. All of the refrigerants (10 different types) and lubricants (seven different types) have been ordered from the manufacturers. To date, the data obtained includes that for R-134a and four lubricants, namely, two esters and two polypropylene glycols (PAGs). Methods for quantifying immiscibility based on observation by different lab workers have been developed.

SCOPE

The scope of the work performed during this report period is as follows:

1. modifying experimental apparatus
2. procuring lubricants and refrigerants
3. developing experimental procedures
4. obtaining initial data for R-134a

SIGNIFICANT RESULTS

Experimental Project Modifications

During this reporting period, the experimental test apparatus was modified considerably. The following modifications were made:

- the high and low temperature baths were separated and reconfigured
- a shaker/vibrator apparatus was developed
- a new evaporator was installed to get lower temperatures
- the number of test cells available were tripled

Test Results

Miscibility testing is nearly complete for R-134a and the following lubricants:

- polypropylene glycol butyl monoether: ICI Emkarox VG32
- penta erythritol ester branched acid: Castrol Icematic SW32
- polypropylene glycol diol: Dow P425
- penta erythritol ester mixed-acid: ICI Emkarate RL244

These tests were performed at lubricant concentrations of 10%, 50%, and 95% over a temperature range of -50°C to 90°C. As specified in the work statement, when cloudiness, precipitate formation, or formation of a second liquid phase is noticed, the mixture is considered immiscible. A summary of the observations for each test reference pair follows.

R-134a and ICI Emkarox VG32 Is fully miscible for all three concentrations over the full temperature range.

R-134a and Castrol SW32 Precipitate formation was observed for the 50% lubricant mixture at a temperature of 0°C. Slight haziness was observed for the 95% mixture at the same temperature. No changes in the nominal 10% mixture were observed.

R-134a and Dow P425 Haziness was observed for the 50% lubricant mixture at a temperature of -20.1°C. Both the nominal 95% and 10% mixtures remained clear throughout the testing.

R-134a and ICI Emkarate RL244 Precipitate formation was observed for the 95% lubricant mixture at -30.3°C. Slight haziness was observed at -38.1°C for the 50% mixture. The 10% mixture remained clear throughout the temperature range.

Tables 1 through 4 provide a summary of the test data for each of the four lubricant and refrigerant pairs.

Table 1 Observations for R-134a: ICI Emkarox VG32 mixtures.

Temperature °C	Nominal 95 Concentration	Nominal 50 Concentration	Nominal 10 Concentration
90	*	*	*
80	*	*	*
76.5	clear	clear	clear
65.1	clear	clear	clear
59.5	clear	clear	clear
53.9	clear	clear	clear
49.2	clear	clear	clear
room temp.	clear	clear	clear
-0.2	clear	clear	clear
-9.6	clear	clear	clear
-20.1	clear	clear	clear
-30.3	clear	clear	clear
-38.1	clear	clear	clear
-50	*	*	*

*data to be taken later

Table 2 Observations for R-134a: Castrol SW32 mixtures.

Temperature °C	Nominal 95 Concentration	Nominal 50 Concentration	Nominal 10 Concentration
90	*	*	*
80	*	*	*
76.5	clear	clear	clear
65.1	clear	clear	clear
59.5	clear	clear	clear
53.9	clear	clear	clear
49.2	clear	clear	clear
room temp.	clear	clear	clear
-0.2	slightly hazy	very small particles throughout	clear
-9.6	slightly hazy	very small particles throughout	clear
-20.1	slightly hazy	very small particles throughout	clear
-30.3	slightly hazy	very small particles throughout	clear
-38.1	slightly hazy	very small particles throughout	clear
-50	*	*	*

*data to be taken later

Table 3 Observations for R-134a: Dow P425 mixtures.

Temperature °C	Nominal 95 Concentration	Nominal 50 Concentration	Nominal 10 Concentration
90	*	*	*
80	*	*	*
76.5	clear	clear	clear
65.1	clear	clear	clear
59.5	clear	clear	clear
53.9	clear	clear	clear
49.2	clear	clear	clear
room temp.	clear	clear	clear
-0.2	clear	clear	clear
-9.6	clear	hazy	clear
-20.1	clear	very hazy	clear
-30.3	clear	very hazy	clear
-38.1	clear	very hazy	clear
-50	*	*	*

*data to be taken later

Table 4 Observations for R-134a: ICI Emkarate RL244 mixtures.

Temperature °C	Nominal 95 Concentration	Nominal 50 Concentration	Nominal 10 Concentration
90	*	*	*
80	*	*	*
76.5	-	clear	clear
65.1	clear	clear	clear
59.5	clear	clear	clear
53.9	clear	clear	clear
49.2	clear	clear	clear
room temp.	clear	clear	clear
-0.2	clear	clear	clear
-9.6	clear	clear	clear
-20.1	clear	clear	clear
-30.3	clear, small particles present	clear	clear
-38.1	clear, small particles present	slightly hazy	clear
-50	*	*	*

*data to be taken later

Nominal Concentration

The refrigerant concentrations given are nominal values for each lubricant-refrigerant test condition. The nominal concentration represents the concentration that exists in the cell when initially charged at room temperature. As the temperature is raised in each cell, the density of the vapor phase increases which results in the transport of refrigerant from the liquid phase to the vapor phase and, hence, an increase in lubricant concentration. However, the volume of the vapor phase decreases due to thermal expansion which diminishes some of the impact of this lubricant concentration increase. The opposite of the above occurs as the temperature of each cell is lowered from room temperature. Specifically, the density of the vapor decreases and the vapor volume increases. The net result is that lubricant composition decreases.

These changes in the liquid composition are small since the vapor volume in each cell is minimized during charging. However, in order to cover the whole temperature range, a 10 to 15% vapor space is required due to thermal expansion and contraction. For this required vapor space, changes in liquid composition are noticeable for refrigerant concentrations lower than 30%. For example, with a 15% vapor volume, the liquid concentration of the R-134a cells tested during this period changed in composition about $\pm 1.5\%$.

Quantification of Observations

A methodology for recording the observed characteristics of each cell has been developed, so that the characteristics reported by different observers will be consistent. Tentative scales of

cloudiness (haziness), precipitate formation, and color are being constructed. In the future, photographs may be taken of cells containing immiscible liquids to be used for reference. However, testing to date has not provided many opportunities to obtain photographs, since most of the cells remained clear throughout the test. The tentative scales are as follows:

Haziness

- 0 = barely detectable
- 1 = light haze
- 2 = medium haze, barely see through
- 3 = very hazy, cannot see through

Color

- 0 = light color, such as yellow
- 1 = medium color
- 2 = dark color

Precipitate Formation

- 0 = hardly noticeable particles
- 1 = small particles
- 2 = large particles

Problems Encountered During Reporting Period

Several minor problems have been encountered during the reporting period. One problem is that when increasing the temperature of a cell, thermal expansion causes the vapor volume to be reduced. If the vapor volume decreases to zero, a cell can potentially rupture. Therefore, when charging the cells, one must be careful to leave enough vapor volume to prevent cell failure. This is the reason that some of the preliminary data was taken at a maximum temperature of 76.5°C. Specifically, these cells were charged with too much refrigerant and lubricant (i.e., too little vapor space).

Another problem limited the data taking at lower temperatures. A leak in the plumbing of the low temperature bath occurred before the -50°C temperature was achieved. This problem will be fixed and the data set will be completed.

COMPLIANCE WITH AGREEMENT

The work statement designated temperatures ranging from 90°C to -50°C in ten degree increments. The exact temperatures (e.g., 90, 80, ..., -50) are not necessarily being achieved. However, steady state temperatures near these temperatures at approximately 10°C increments will be achieved and recorded. Any immiscibility that occurs, which will allow identification for Phase II, will certainly be observable by using this approach. The work statement also specified refrigerant concentrations of 95, 50, and 10%. Refrigerant concentrations will be $\pm 2\%$ from these values in most cases, and they will always be known to within $\pm 0.5\%$.

PRINCIPAL INVESTIGATOR EFFORT

Dr. Michael Pate is the Principal Investigator for this project. During this reporting period of 6 February to 31 March, Dr. Pate devoted a total of seventy-eight labor hours (25% of his available work hours) on this project.

END

**DATE
FILMED**

7 / 20 / 92