DOE/ID/12778--3

DE92 016809

DEVELOPMENT OF HIGH TEMPERATURE CATALYTIC MEMBRANE REACTORS

Topical Report

February 1992

Work Performed Under Contract No. DE-FC07-88ID12778

**Prepared for the
U.S. Department of Energy
Under DOE Idaho Field Office
Sponsored by the Office of the Assistant Secretary
for Conservation and Renewable Energy
Office of Industrial Technologies
Washington, D.C.**

**Prepared by
Aluminum Company of America
1135 William Pitt Way
Pittsburgh, PA 15238**

Table of Contents

- I. Reactor System
- II. Reaction Results
 - A. Single Stage vs. Two Stage Packed Bed
 - B. Two Stage Packed Bed vs. Hybrid Membrane Reactor
 - 1. Conversion
 - 2. Selectivity
 - 3. Effect of $\text{H}_2\text{O}/\text{EB}$ Ratio
 - 4. Permeability under Reaction Conditions
 - 5. Effect of N_2 in Feed Flow
- III. Outside Interactions
- IV. Interaction with University of Wisconsin
- V. Next Steps

Executive Summary

Progress continued in 1991 toward the development of a commercially viable ceramic membrane reactor for the dehydrogenation of ethylbenzene to styrene. The primary focus was the design, construction, and startup of a modified reactor system and membrane module in order to overcome deficiencies in the original system that prevented experimental simulation of the industrial operation.

In the modified system, liquid water and ethylbenzene feeds are delivered via syringe pumps rather than HPLC pumps so that the low flowrates required to duplicate industrial reactor space velocities are attainable. Stable vapor flows into the reactor are generated in thermosyphon style vaporizers. Vapor phase inlet and outlet pressures around the reactor are monitored with high temperature pressure transducers. Isothermal operation of the reactor is accomplished by using a 7 zone furnace with each zone independently variable in place of the former 2 zone furnace. The modified module contains a 4 point thermocouple which monitors temperatures along the catalyst bed. Isothermal operation within $\pm 1^\circ\text{C}$ is routinely achieved. Three single point thermocouples are employed to monitor temperatures along the permeate side of the reactor. Simultaneous on-line analysis of the permeate and reject streams is accomplished with two dual FID/TCD equipped gas chromatographs. An analytical protocol has been developed to analyze the entire spectrum of organic and nonorganic compounds in the effluent streams with 30 minute turnaround time.

Promising preliminary results obtained with this system showed a 4% yield enhancement to styrene for a hybrid packed bed-ceramic membrane reactor compared to a traditional two stage packed bed. This enhancement was achieved with no loss in styrene selectivity. Data analysis showed this improvement to be statistically significant at 95% confidence limits. The hybrid reactor configuration mimics the simplest implementation of a ceramic membrane reactor, duplicating the use of the membrane reactor as an add on stage to the existing reactor train. Efforts in 1992 will focus on optimizing reactor performance to finalize the total enhancement attainable from this technology.

Two presentations were made at national meeting to update the scientific community on project progress. Additionally, discussions were held with two potential endusers on the possibility of future joint development. Information is currently being exchanged on a nonconfidential basis and discussions are continuing.

One iron oxide membrane was received and from the University of Wisconsin and evaluated in 1991. Characterization revealed insufficient coating of the $0.2\mu\text{m}$ support. Discussions were also held and recommendations made to improve the operating performance of the Wisconsin reaction system

Current efforts are focused on rebuilding the reaction system following the move from Alcoa Separation Technology, Inc.'s Warrendale facility to the University of

Pittsburgh Applied Research Center. This should be completed by the end of February. A factorial experiment is being designed to organize the evaluation of process parameters for further optimization of the process. Additionally, a feasibility study has been initiated to evaluate the potential application of ceramic membrane reactors for the industrially important dehydrogenation of isobutane to isobutene, an intermediate for the octane enhancer MTBE.

Introduction

Significant progress was made in 1991 on the development of ceramic membranes as catalytic reactors. Efforts were focused on the design, construction and startup of a reactor system capable of duplicating relevant commercial operating conditions. With this system, yield enhancement was demonstrated for the dehydrogenation of ethylbenzene to styrene in a membrane reactor compared to the standard packed bed configuration. This enhancement came with no loss in styrene selectivity. During operation, coke deposition on the membrane was observed, but this deposition was mitigated by the presence of steam in the reaction mixture and a steady state permeability was achieved for run times in excess of 200 hours. Work began on optimizing the membrane reactor by exploring several parameters including the effect of N_2 diluent in the reaction feed and the effect of a N_2 purge on the permeate side of the membrane.

This report details the experimental progress made in 1991. Interactions with the University of Wisconsin on this project are also summarized. Finally, current status of the project and next steps are outlined.

Reactor System

By late 1990 it was obvious that the original reactor design was inadequate for simulating real commercial operating condition for styrene production. Liquid hourly space velocities (LHSV) in that system were nearly two orders of magnitude greater than the 0.4 hr^{-1} to 0.6 hr^{-1} employed industrially. This limitation was due to the use of HPLC pumps for feeding the reactor. These high flowrates resulted in rapid catalyst deactivation caused by potassium leaching and subsequent coking. Additionally, higher operating temperatures were required to attain reasonable conversions. Also, isothermal operation necessary for rigorous evaluation of the process was unachievable using the two zone furnace originally employed. Finally, the original module design with a single thermocouple in the catalyst bed prevented monitoring of the temperature profile in the reactor. Because of these limitations, a thorough redesign of the system was undertaken in 1991.

The modified system is shown schematically in Figure 1. Water and ethylbenzene liquids are fed to vaporizers via variable flow Harvard Apparatus syringe pumps. These pumps can deliver the liquid feed rates of approximately $20 \mu\text{L}/\text{minute}$ necessary to achieve LHSV's of 0.4 hr^{-1} . The vaporizers are of thermosyphon design. In the lower section, large volumes of vapor are generated. Much of this flow condenses in a cold arm on the side. A large circulating flow of vapor is thus set up. A small portion of this recirculation is drawn through a needle valve on the top of the vaporizer and fed to the system. Ethylbenzene and water vapor are carried to the reactor by flowing N_2 .

The membrane reactor is housed in a seven zone furnace. Three zones heat the preheater section and four zones are localized around the membrane module. The four zones around the module can be independently adjusted to yield an isothermal temperature profile along the membrane reactor. Temperature

FIGURE 1

profiles within $\pm 1^\circ\text{C}$ are routinely achieved. A N_2 purge is provided on the permeate side of the membrane module. High temperature pressure transducers are located at the inlet and outlet of the reactor to monitor feed, reject, and permeate pressures.

A bypass is installed around the reactor. During startup, the feed flow is diverted around the reactor so that steam and ethylbenzene vapor flows can stabilize. The reactor is heated to temperature at approximately $10^\circ\text{C}/\text{minute}$ in flowing N_2 . Once the feed flow and reactor temperature stabilize, the feed is switched into the reactor. This procedure protects the catalyst and membrane from the flow fluctuations that can occur during this transient period.

A detailed schematic of the membrane module is shown in Figure 2. The ceramic membrane is sealed in the stainless steel module via packing glands and graphite ribbon packing. The membrane tube is packed with a commercial, potassium-promoted iron oxide styrene catalyst from United Catalysts. The commercial pellets are crushed and sieved through 14 mesh onto 28 mesh before packing to increase packing density in this benchscale configuration. A four point thermocouple is placed in the catalyst bed to monitor reaction temperatures at the inlet and outlet of the reactor as well as at points 1/3 and 2/3 of the way along the bed. In addition, three single point thermocouples are placed along the shell side of the module to monitor permeate temperatures.

Permeate and reject streams exit the furnace and flow to separate dual FID/TCD gas chromatographs for simultaneous online sampling. The analytical protocol uses a Hayesep D column on the TCD side and a Porapak Q column on the FID side. H_2 , N_2 , CO , CO_2 , CH_4 , and water are analyzed on the TCD side. The Hayesep D column gives a particularly nice peak for water with no detectable permanent holdup and little peak tailing. Methane, ethylene, ethane, benzene, toluene, ethylbenzene, and styrene are analyzed on the FID side. The sample is injected at 40°C . This temperature is held for 2 minutes before ramping at $25^\circ\text{C}/\text{min}$ to 245°C followed by another hold period. All products elute within 20 minutes. Total turnaround for the analysis is 30 minutes.

The streams exit the gc's and pass through condensers. The condensable fractions are collected and the gas flow rates are measured with bubble meters before venting to a fume hood.

Reaction Results

The system described above enables evaluation of ethylbenzene dehydrogenation under realistic industrial conditions. Typical industrial operating conditions are summarized in Table 1. The initial commercialization of membrane reactors for styrene production will likely be as an add-on stage to an existing series of packed bed reactors. This configuration would minimize capital expense and risk to the end user while adding flexibility to the existing process. With this consideration, experimentation was undertaken in 1991 to compare the performance of a packed bed reactor with an add-on stage ceramic membrane reactor to that of a packed bed reactor with an additional packed bed stage.

FIGURE 2

Ceramic Membrane Reactor

TABLE 1

ETHYLBENZENE DEHYDROGENATION

INDUSTRIAL OPERATING CONDITIONS

CATALYST	Cr, K/Fe ₂ O ₃
PRESSURE	≤ 20 PSIG
TEMPERATURE	580°C - 610°C
TEMPERATURE PROFILE	ISOTHERMAL, ADIABATIC
H ₂ O/EB	6:1 - 14:1
EB LHSV	0.4 hr ⁻¹ - 0.6 hr ⁻¹
ETHYLBENZENE CONVERSION	60% - 70%
STYRENE YIELD	90% - 95%

FIGURE 3

FIGURE 4

Ceramic Membrane Reactor vs. Packed Bed Reactor

TABLE 2

Ceramic Membrane Reactor vs. Packed Bed Reactor

Styrene Yield (%)

Temperature (°C)	Ceramic Membrane	Packed Bed
530	46	-
535	-	41
550	58	54
575	72	65
600	77	73

TABLE 3

Ceramic Membrane Reactor vs. Packed Bed Reactor

Selectivities

Temperature (°C)	Styrene		Benzene		Toluene	
	Membrane	Packed Bed	Membrane	Packed Bed	Membrane	Packed Bed
530	0.98	-	0.01	-	0.01	-
535	-	0.98	-	0.01	-	0.01
550	0.96	0.96	0.02	0.02	0.03	0.02
575	0.94	0.95	0.02	0.02	0.04	0.03
600	0.93	0.93	0.02	0.03	0.05	0.04

FIGURE 5

FIGURE 6

FIGURE 7

FIGURE 8

Packed Bed Reactor

Single Stage Packed Bed vs. Two Stage Packed Bed

In the industrial operation, the discharge from the reactor train is near equilibrium. Adding another packed bed would result in no further styrene production, but side reactions to benzene and toluene would continue since these reactions consume hydrogen. The net result would be a loss of styrene yield. The first study undertaken evaluated the effect of adding an additional packed bed stage to a single packed bed reactor. Results of this study are shown in Figure 3.

The single stage packed bed was prepared by packing a stainless steel tube mounted in the membrane module with 9.0g of crushed catalyst. The two stage reactor was assembled by packing an additional 7.5g of catalyst in the module preheater. Flows were set to yield an ethylbenzene LHSV of 0.4 hr⁻¹ in the two stage configuration. The same flow rates were used in the single stage mode resulting in an ethylbenzene LHSV of 0.75 hr⁻¹. A water to ethylbenzene molar ratio of 9 was targeted. The N₂ carrier flowrate in the feed was fixed at a 9:1 N₂:ethylbenzene molar ratio. Inlet pressure to the reactor was fixed at 5 psig.

As can be seen in Figure 3, the two stage packed bed out performed the single stage reactor at lower reaction temperatures. However, as reaction temperatures of 600°C were approached, styrene yields from the single stage and two stage reactors were nearly identical. This suggests that at the lower temperatures the single stage reactor was not fully equilibrated. This is due to the higher space velocities employed with the single stage reactor vs. the two stage reactor. At 600°C the single stage reactor appears to be fully equilibrated and the addition of a second stage resulted in no further increase of styrene yield.

Two Stage Packed Bed vs. Packed Bed Ceramic Membrane Hybrid Reactor

The next study compared the performance of a two stage packed bed with that of a packed bed followed by a ceramic membrane reactor. The results are summarized in Figures 4-8 and Tables 2 and 3. The two stage packed bed was configured as described above. For the hybrid reactor, the stainless steel tube in the module was replaced with a 40Å pore size ceramic membrane packed with 9.0g of crushed commercial catalyst. Flows were fixed to yield ethylbenzene LHSV's of 0.4 hr⁻¹ for both reactors. Inlet pressures were set at 5 psig resulting in a pressure ratio of 0.33 (average tube side pressure/permeate side pressure) for the membrane reactor. A partial set of typical readings for a run at 600°C in the hybrid reactor are shown in the appendix. These readings include flowrates, pressures, temperature profiles in the catalyst bed as well as permeate zone, and analytical results for both the reject and permeate effluents.

As shown in Figure 4 and Table 2, the hybrid reactor outperformed the packed bed reactor at each reaction temperature. Styrene yields were enhanced in the hybrid reactor by about 4% throughout the range of temperatures investigated. Table 3 summarizes data on reaction selectivity for both the packed bed and hybrid reactors. Focusing first on the packed bed data it can be seen that as expected, increasing yield with increasing reaction temperature resulted in a dropoff of

selectivity to styrene. Comparing these results with those from the hybrid reactor, it can be seen that the 4% enhancement in styrene yield in the hybrid reactor comes with no loss in selectivity to styrene.

The results shown in Figure 4 and Tables 2 and 3 represent a condensation of all the data points taken for each reaction run. The results of a typical run are shown in Figure 5 for the membrane reactor at 600°C. Despite attempts to carefully control feed flowrates, some variation in the water/ethylbenzene ratio occurs. In analyzing the data, styrene yield is plotted vs. this ratio. Styrene yield increases with water/ethylbenzene ratio then plateaus at values above about 12. This effect is due to a combination of steam reacting with deposited carbon to prevent catalyst deactivation and steam dilution of the reaction mixture thereby shifting the reaction equilibrium. At high ratios, the beneficial effect of lowering H₂ partial pressure is offset by dilution of reactant ethylbenzene partial pressure. The commercial catalyst employed is designed for a water/ethylbenzene ratio of 9-10 which approximates the break point in the curve in Figure 5. Figure 6 shows a linear regression of the data over the range of water/ethylbenzene ratios from 8 to 12. Data in this range are well fit by a straight line. The regression equation is then used to determine the styrene yield at a water/ethylbenzene ratio of 10. The variation of styrene yield with water/ethylbenzene ratio and data regression for a run in the packed bed are shown in Figures 7 and 8 respectively for comparison purposes. The method of data analysis described above was used for all results in Figure 4 and Tables 2 and 3.

Membrane Permeability under Reaction Conditions

The dehydrogenation of ethylbenzene to styrene also results in significant carbon deposition on the catalyst necessitating the addition of steam to react with the carbon and prevent catalyst deactivation. For the membrane reactor, the impact of carbon deposition on membrane permeability was an additional concern. Figure 9 shows the permeability of the membrane as a function of time on stream at a reaction temperature of 600°C.

Characterization studies have shown that the permeability of fresh membranes is typically about 70 m³/m²/hr/atm. Thermal treatment at 600°C drives off adsorbed moisture and results in an increase of permeability to 110 m³/m²/hr/atm without any change in the 40Å nominal pore size. As can be seen from Figure 9, the steady state permeability under reaction conditions is approximately 2 m³/m²/hr/atm. These permeability values are determined by converting the observed molar flux at reaction temperature to a volumetric flux at STP. This level of permeation suggests that carbon does deposit on the membrane in the initial stages of reaction, but that the presence of steam in the reaction mixture results in a dynamic equilibrium between carbon deposition and removal.

A second concern that arose from results with the original high flow reactor system was the effect of alkali leaching from the catalyst on catalyst activity and membrane stability. In the original system, activity declined dramatically within 12 hours as nearly one third of the alkali in the catalyst was lost. Part of this alkali deposited on the membrane resulting in significant pore size enlargement as the

alkali accelerated the thermodynamic transition from $\gamma\text{-Al}_2\text{O}_3$ to other transitional forms of alumina. This enlargement in turn resulted increased permeation through the membrane along with concurrent loss in membrane gas separation capability. As can be seen from the reaction results discussed above, catalyst activity remains constant over over long run times in the modified system. In addition, as can be seen from the permeability results in Figure 9, no deleterious effect of alkali on membrane performance has been observed. This is due to operating at ethylbenzene LHSV's of 0.4 hr^{-1} with water to ethylbenzene ratios near 10 in the modified system. This compares to achievable minimum space velocities over 100 times greater in the original system.

The critical requirement for permeation is that sufficient H_2 flux be present so that the reactor does not reequilibrate and thereby behave like a packed bed. This appears to be the case here, although this permeability is probably not the optimum. It is possible that a higher H_2 permeability would result in further enhancement of styrene yield. However, reduced permeability can benefit the reactor by preventing bypassing of the catalyst bed by the reactant ethylbenzene. Membrane permeability and pore size distribution after longterm exposure to reaction as well as alkali leach rates from the catalyst are targeted for study as part of the optimization of the hybrid reactor.

Effect of N_2 in the Feed

Just as the steam added to the reactor feed can enhance styrene yield to a certain point by reducing the partial pressure of H_2 in the catalyst bed, the N_2 used as a carrier flow from the vaporizers to the reactor can have a similar effect. This is demonstrated in Figure 10 for the hybrid reactor at 600°C . A N_2 flowrate of 40 cc/min results in a feed N_2 /ethylbenzene ratio of about 9. As can be seen in Figure 10, reducing the N_2 flow from 40 cc/min to 20 cc/min results in a styrene yield decline from 77% to 69%. Styrene yield drops further to 60% when the N_2 flow is lowered to 10 cc/min. The effect of lower N_2 feed flows on the performance of the packed bed reactor has not yet been evaluated. However, the impact should be at least as great and possibly greater. The increased H_2 partial pressure resulting from the loss of diluent N_2 creates a larger H_2 permeation driving force in the membrane reactor whereas in the packed bed the total effect of increased H_2 partial pressure would be to equilibrate the reaction and decrease the styrene yield. This will be experimentally verified in an upcoming study.

Outside Interactions

During 1991, several presentations were made at national meetings. A presentation at the summer national meeting of the AIChE in Pittsburgh in August highlighted the reactor modifications that were made and outlined the potential reactor performance based on model simulations. A presentation at the 7th Symposium on Separation Science and Technology for Energy Applications in Knoxville in October summarized several of the important experimental results obtained in 1991.

Discussions were also held with two potential endusers in 1991. Several meetings were held with a major American petrochemical concern to discuss project status and the potential for future joint development. These talks are continuing on a nonconfidential basis pending the outcome of budgetary decisions on their part and the resolution of issues related to the sale of Alcoa Separations Technology, Inc. to U.S. Filter. Discussions were also held with a major American engineering firm involved in the design and construction of styrene and other dehydrogenation plants. Process performance requirements were discussed and information will be exchanged on a nonconfidential basis in the short term.

Interaction with the University of Wisconsin

One iron oxide coated membrane was received from the University of Wisconsin in August. This membrane was characterized via gas permeation, pore size distribution, and SEM analysis. The results have been summarized in a report issued in September which can be found in the appendix. Briefly, the membrane permeability was approximately $500 \text{ m}^3/\text{m}^2/\text{hr}/\text{atm}$, similar to that of the $0.2 \text{ }\mu\text{m}$ support. Pore size distribution analysis showed no pores smaller than $300\text{\AA}$ diameter. Evidence of the presence of iron oxide was observed from SEM but large portions of the underlying $0.2\text{ }\mu\text{m}$ support were also observed suggesting incomplete coating of the support.

Discussions were also held with Professor Anderson and Fernando Tiscareno regarding coking problems experienced in the Wisconsin reactor. Recommendations for system improvements involving feed delivery, start up procedures, and analytical methods were summarized in a report issued in November which can also be found in the appendix.

Informal discussions were held throughout the year with Dr. Walter Zeltner to exchange project progress information and to manage membrane inventory issues.

Next Steps

Currently the reaction system is being rebuilt following the move from the Alcoa Separations Technology, Inc. facility in Warrendale to the University of Pittsburgh Applied Research Center. Several process improvements are being incorporated into the system at this time including a shortening of reactor effluent line, the capacity for steam purge, the capacity for vacuum purge, and the capacity for counter-current purge. In addition, a factorial experimental plan is being developed with the assistance of Mr. Mike Domagala, a statistician with the Alcoa Corporate Quality Assurance. This experimental plan will be used to identify the effect of various process parameters on reactor performance so that process optimization can proceed in an organized fashion. The details of this plan will be summarized in a future update.

Information from enduser contacts suggest significant interest in application of this technology to other reactions in addition to ethylbenzene dehydrogenation.

FIGURE 9

FIGURE 10

The dehydrogenation of isobutane to isobutene, a major intermediate for the manufacture of the octane enhancer MTBE, is of particular interest. Information has been exchanged with Dr. Ronald Minet of Medalert, Inc. to begin a feasibility study of this process. Additionally, an internal literature search and model simulation studies have been initiated for this reaction.

APPENDIX

Ceramic Membrane Reactor: Ethylbenzene to Styrene; 2 Stage Reactor
9/23/91 to 9/26/91
T=530°C-600°C ; Vary Temperature

	A	B	C	D	E	F	G	H
1								
2								
3								
4								
5								
6								
7								
8								
9								
10	09-26-91	03:30PM	600.00	4.60	0.70	0.80	42.90	9.50
11		04:00PM	600.00	4.30	0.80	0.80	50.00	10.30
12		04:30PM	600.00	4.40	0.80	0.80	42.90	8.30
13		05:00PM	600.00	4.00	0.70	0.70	46.20	9.70
14		05:30PM	600.00	4.10	0.70	0.70	46.20	9.50
15		06:00PM	600.00	4.00	0.80	0.70	40.00	10.00
16		06:30PM	600.00	3.90	0.70	0.70	46.20	8.20
17		07:00PM	600.00	4.90	0.90	0.80	42.90	8.20
18		07:30PM	600.00	4.10	0.80	0.80	42.90	8.50
19		08:00PM	600.00	4.40	0.80	0.80	42.90	9.20
20		08:30PM	600.00	4.30	0.80	0.80	42.90	9.70
21		09:00PM	600.00	4.50	0.80	0.80	46.20	8.00
22		09:30PM	600.00	4.70	0.80	0.80	46.20	10.00
23		10:00PM	600.00	4.40	0.70	0.70	46.20	8.70
24		10:30PM	600.00	4.70	0.80	0.80	42.90	9.80
25		11:00PM	600.00	4.40	0.80	0.80	42.90	9.70
26		11:30PM	600.00	4.60	0.80	0.80	42.90	9.80
27	09-27-91	12:00AM	600.00	4.60	0.80	0.80	42.90	6.30
28		12:30AM	600.00	4.50	0.70	0.80	42.90	10.00
29		01:00AM	600.00	4.50	0.70	0.80	42.90	8.70
30		01:30AM	600.00	4.30	0.80	0.80	46.20	9.38
31		02:00AM	600.00	4.20	0.80	0.80	42.90	9.38
32		02:30AM	600.00	4.30	0.80	0.80	42.90	9.38
33		03:00AM	600.00	4.40	0.80	0.80	42.90	9.52
34		03:30AM	600.00	4.30	0.80	0.70	42.90	10.50
35		04:00AM	600.00	4.50	0.80	0.80	46.20	9.83
36		04:30AM	600.00	4.40	0.80	0.80	46.20	9.83
37		05:00AM	600.00	4.40	0.80	0.80	42.90	9.83

Reactor Raw Data

	I	J	K	L	M	N	O	P
1								
2								
3								
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								
33								
34								
35								
36								
37								

Reactor Temperatures

	Q	R	S	T	U	V	W	X
1								
2								
3								
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								
33								
34								
35								
36								
37								

Reject Raw Analysis

	Methane (Moles)	Ethylene (Moles)	Ethane (Moles)	Benzene (Moles)	Toluene (Moles)	Ethylbenzene (Moles)	Styrene (Moles)
10	4.47E-09	0.00E+00	0.00E+00	5.80E-09	1.45E-08	5.46E-08	2.48E-07
11	5.51E-09	3.01E-10	0.00E+00	6.70E-09	1.63E-08	7.04E-08	2.91E-07
12	4.61E-09	0.00E+00	0.00E+00	5.82E-09	1.46E-08	4.86E-08	2.41E-07
13	4.98E-09	0.00E+00	0.00E+00	6.38E-09	1.61E-08	4.81E-08	2.51E-07
14	4.33E-09	0.00E+00	0.00E+00	5.29E-09	1.41E-08	6.05E-08	2.63E-07
15	4.52E-09	0.00E+00	0.00E+00	5.79E-09	1.49E-08	4.42E-08	2.34E-07
16	4.67E-09	0.00E+00	0.00E+00	5.93E-09	1.53E-08	4.80E-08	2.42E-07
17	4.02E-09	0.00E+00	0.00E+00	5.14E-09	1.37E-08	4.25E-08	2.16E-07
18	4.81E-09	0.00E+00	0.00E+00	5.92E-09	1.51E-08	5.91E-08	2.57E-07
19	4.24E-09	0.00E+00	0.00E+00	5.28E-09	1.35E-08	4.40E-08	2.29E-07
20	4.50E-09	0.00E+00	0.00E+00	5.71E-09	1.50E-08	4.61E-08	2.42E-07
21	5.83E-09	0.00E+00	0.00E+00	6.90E-09	1.70E-08	9.75E-08	3.45E-07
22	5.62E-09	0.00E+00	0.00E+00	6.67E-09	1.64E-08	9.38E-08	3.40E-07
23	4.79E-09	0.00E+00	0.00E+00	5.73E-09	1.47E-08	7.14E-08	2.91E-07
24	4.20E-09	0.00E+00	0.00E+00	5.32E-09	1.42E-08	5.09E-08	2.47E-07
25	4.31E-09	0.00E+00	0.00E+00	5.43E-09	1.47E-08	5.49E-08	2.54E-07
26	4.36E-09	0.00E+00	0.00E+00	5.51E-09	1.49E-08	5.70E-08	2.64E-07
27	4.02E-09	0.00E+00	0.00E+00	5.11E-09	1.41E-08	4.89E-08	2.39E-07
28	4.06E-09	0.00E+00	0.00E+00	5.13E-09	1.42E-08	5.35E-08	2.50E-07
29	4.46E-09	0.00E+00	0.00E+00	5.62E-09	1.54E-08	5.66E-08	2.61E-07
30	5.06E-09	0.00E+00	0.00E+00	6.11E-09	1.63E-08	7.55E-08	3.07E-07
31	3.78E-09	0.00E+00	0.00E+00	4.96E-09	1.38E-08	3.80E-08	2.13E-07
32	3.91E-09	0.00E+00	0.00E+00	4.98E-09	1.40E-08	4.66E-08	2.33E-07
33	4.52E-09	0.00E+00	0.00E+00	5.64E-09	1.51E-08	6.38E-08	2.81E-07
34	5.70E-09	0.00E+00	0.00E+00	6.64E-09	1.69E-08	1.19E-07	3.80E-07
35	5.70E-09	0.00E+00	0.00E+00	6.62E-09	1.62E-08	1.18E-07	3.77E-07
36	4.73E-09	0.00E+00	0.00E+00	5.61E-09	1.48E-08	8.92E-08	3.11E-07
37	4.44E-09	0.00E+00	0.00E+00	5.44E-09	1.47E-08	6.46E-08	2.76E-07

	Y	Z	AA	AB	AC	AD	AE	AF
1								
2								
3								
4								
5								
6								
7								
8								
9								
10								
11								
12								
13								
14								
15								
16								
17								
18								
19								
20								
21								
22								
23								
24								
25								
26								
27								
28								
29								
30								
31								
32								
33								
34								
35								
36								
37								

Reject Raw Analysis

[illegible]

	AO	AP	AQ	AR	AS	AT	AU	AV
1								
2								
3								
4								
5								
6	0.00							
7	Styrene	H2	N2	CO	CO2	H2O		
8	(Counts)	(Moles)	(Moles)	(Moles)	(Moles)	(Moles)		
9								
10	9133984.00	2.58E-07	2.72E-06	0.00E+00	3.05E-08	4.80E-06		
11	18637824.00	4.77E-07	4.43E-06	0.00E+00	4.38E-08	2.15E-06		
12	13430871.99	3.57E-07	3.85E-06	0.00E+00	4.17E-08	3.18E-06		
13	13361071.99	3.93E-07	3.90E-06	0.00E+00	4.11E-08	3.05E-06		
14	10707080.00	3.21E-07	3.37E-06	0.00E+00	3.99E-08	3.91E-06		
15	12054655.99	3.42E-07	3.90E-06	0.00E+00	4.21E-08	3.17E-06		
16	12427447.99	3.65E-07	3.95E-06	0.00E+00	4.27E-08	3.10E-06		
17	10331784.00	3.29E-07	3.53E-06	0.00E+00	4.06E-08	3.72E-06		
18	14573584.00	3.97E-07	3.82E-06	0.00E+00	3.96E-08	3.13E-06		
19	10260296.00	3.24E-07	3.60E-06	0.00E+00	4.23E-08	3.61E-06		
20	10742775.99	3.32E-07	3.46E-06	0.00E+00	4.03E-08	3.76E-06		
21	10172456.00	2.34E-07	1.65E-06	0.00E+00	2.39E-08	6.07E-06		
22	17175680.00	4.81E-07	3.60E-06	0.00E+00	4.31E-08	3.21E-06		
23	14112920.00	3.91E-07	3.35E-06	0.00E+00	4.52E-08	3.69E-06		
24	14165047.99	3.85E-07	3.59E-06	0.00E+00	4.41E-08	3.44E-06		
25	11623167.99	3.34E-07	3.28E-06	0.00E+00	3.80E-08	3.93E-06		
26	13092952.00	3.67E-07	3.45E-06	0.00E+00	4.33E-08	3.68E-06		
27	6375725.00	1.95E-07	1.86E-06	0.00E+00	2.72E-08	5.97E-06		
28	12505952.00	3.77E-07	3.65E-06	0.00E+00	4.68E-08	3.41E-06		
29	12958520.00	3.83E-07	3.57E-06	0.00E+00	4.46E-08	3.48E-06		
30	14347503.99	4.10E-07	3.72E-06	0.00E+00	4.23E-08	3.21E-06		
31	10705280.00	3.41E-07	3.91E-06	0.00E+00	4.63E-08	3.21E-06		
32	11619656.00	3.56E-07	3.72E-06	0.00E+00	4.55E-08	3.38E-06		
33	13387736.00	3.90E-07	3.43E-06	0.00E+00	4.24E-08	3.63E-06		
34	17771263.99	4.97E-07	3.36E-06	0.00E+00	4.31E-08	3.42E-06		
	18340672.00	4.91E-07	3.60E-06	0.00E+00	4.30E-08	3.13E-06		
	15683464.00	4.34E-07	3.48E-06	0.00E+00	4.23E-08	3.43E-06		
	12728727.99	3.75E-07	3.47E-06	0.00E+00	4.41E-08	3.64E-06		

Permeate Raw Analysis

September 16, 1991

Professor Mark Anderson
Water Chemistry Program
University of Wisconsin-Madison
660 North Park Street
Madison, Wisconsin 53706

Attn: Professor Mark Anderson

Dear Mark,

Enclosed are the SEM micrographs and photographs of the Fe_2O_3 membrane coated on a $0.2\mu\text{m}$ Membralox® support that I received from Walt in August. I passed along the permeability and pore size distribution result to Walt at the time we received the membrane.

As you may recall, the room temperature N_2 permeability of the membrane was approximately $500 \text{ m}^3/\text{m}^2/\text{hr}/\text{atm}$ and pore size analysis indicated no pores smaller than $300\text{\AA}$ diameter. The permeability is similar to that observed for the $0.2\mu\text{m}$ support.

From the enclosed photograph you can see that the support surface has a light orange discoloration indicating that some Fe_2O_3 did coat the surface. Also noticeable were two thin stripes that were darker in color. In the SEM we looked at both the lightly colored and and darker portions.

The details observable from the micrographs of the lighter sections show the grain structure typical for the $0.2\mu\text{m}$ Al_2O_3 support. In some areas the presence of Fe_2O_3 particles can be detected (Micrograph #1), but the deposits are not sufficient to fully cover the support. In other areas, very few Fe_2O_3 particles are observed (Micrograph #2). The micrograph of the dark stripe (Micrograph #3) shows a heavier coating of Fe_2O_3 , but even there some of the underlying support can be seen. A number of pinhole defects are also observable.

I returned the unused portions of this membrane to Walt shortly after we completed the permeability and pore size analysis in August. When we last spoke,

he indicated that a new student would be taking over the synthesis and was getting ready to prepare new sols. When additional materials are ready for analysis, please feel free to send them along.

I noticed that you have a presentation at the Separation Science and Technology for Energy Applications Symposium in Knoxville in October. I plan to attend and look forward to talking with you there. If there is anything that I can help with in the meantime, please feel free to call me at (412) 772-1434.

Sincerely,

George Gallaher
Senior Research Engineer

cc: Dr. Blaine Brown w/photographs
Mr. William Sonnett

November 4, 1991

Professor Mark Anderson
Water Chemistry Program
University of Wisconsin-Madison
660 North Park Street
Madison, Wisconsin 53706

Attn: Professor Mark Anderson

Dear Mark,

Following our discussions in Knoxville, I talked with Fernando Tiscareno about the operation of your reactor system in order to help solve the problems you have been experiencing with coking under ethylbenzene dehydrogenation conditions. The following summarizes that conversation and includes some suggestions for improved operation.

According to Fernando, he is feeding liquid ethylbenzene and water to vaporizers via a multistage peristaltic pump. He says that flowrates < 0.1 cc/min (estimated to be 60 μ L/min) are attained. These liquids are fed to two sections of straight, 1/16" diameter, heat traced tubes that serve as vaporizers. The flow is then directed to a single stage reactor. Approximately 9 g of Shell 105 catalyst are packed in the membrane tube. The temperature profile in the reactor is controlled by monitoring the temperature of the feed to the reactor, the exhaust from the reaction zone, and the temperature of the permeate side of the membrane at a point half way down the membrane module. During startup, he heats the reactor to 200°C in N₂, then feeds the reactor with pure steam. Once this flow is stabilized, he adds ethylbenzene to the feed. He then begins heating the reactor to the desired operating temperature at 1°C-2°C/min. Reaction products are analyzed on a single gas chromatograph with dual TCD/FID detectors. I believe he is using a mole sieve column on the TCD side and a Porapak Q column on the FID side. The analytical protocol involves ramping the gc from room temperature to 180°C during analysis.

My first concern is with the use of a peristaltic pump to feed the liquids. By the nature of their design, peristaltic pumps generate a pulsating liquid flow. This pulsation is greatest when the pumps are operated at low flowrates such as in

this case. The use of straight tube vaporizers will exacerbate this problem. Our experience with straight tube vaporizers was that the tube began to fill with liquid which then rapidly evaporated, emptying the tube. Some time was then required to refill the tube. For us this resulted in a fluctuation in feed flow which we eliminated by going with a thermosyphon style vaporizer from which we draw a small vapor flow. This fluctuation is important since it can result in periods where the reactor is exposed to high concentrations of ethylbenzene which will result in carbon deposition.

At 60 $\mu\text{L}/\text{min}$, the feed flows also seem too high. The nominal liquid hourly space velocities used for this reaction are 0.4 hr^{-1} to 0.6 hr^{-1} . This would be calculated by dividing the liquid volumetric feedrate of ethylbenzene by the volume of catalyst in the reactor. Fernando may be using the geometric volume of the reactor for this calculation. With a 60 $\mu\text{L}/\text{min}$ feed of ethylbenzene into a 9 g bed of catalyst (density of the catalyst is estimated at 4.6 g/ml as determined for our United catalyst), this works out to a LHSV of about 1.8 hr^{-1} . This is three to four times higher than the typical values.

The current method of temperature control places no thermocouples in the catalyst bed itself. By maintaining the temperature on the permeate side of the membrane at the same level as the inlet and exhaust, it is likely that a nonisothermal profile exists in the catalyst bed. We have observed that when the temperature profile from the four points we monitor in the catalyst bed are isothermal, a temperature gradient exists along the permeate side.

The startup procedure being used exposes the catalyst and the membrane to pure steam for some period of time. While the temperature of this exposure is moderate compared to actual reaction conditions, we have found from hydrothermal stability studies that temperatures of $>500^\circ\text{C}$ are required to drive off adsorbed moisture from the membrane. Any moisture that accumulates during this startup may remain until this higher operating temperature is achieved, and I would be concerned that some material modification may take place. We have installed a bypass to our reactor that allows us to stabilize both water and ethylbenzene flows before feeding the reactor at the operating temperature. With this, the reactor sees only the final reaction mixture and is never exposed to single component flows.

The existing analytical setup does not allow for simultaneous sampling of both the permeate and reject streams. Turn around time for the analysis is probably 30 minutes or more. System conditions can fluctuate during this time, making analysis of the results more difficult. Also I feel that the use of a mole sieve column on the TCD side of the chromatograph is not the best choice. This column will retain much of the water coming from the sample and hamper reproducibility of the result. Fernando said that he has difficulty eluting the aromatic components using this protocol. This is probably due to the low final temperature used in the temperature programmed portion of the method. For our analysis we use a Hayesep D column on the TCD side and a Porapak Q column on the FID side. H_2 , N_2 , CO , CO_2 , CH_4 , and water are analyzed on the TCD side. The Hayesep D column gives a particularly nice peak for water with no detectable

permanent holdup and little peak tailing. Methane, ethylene, ethane, benzene, toluene, ethylbenzene, and styrene are analyzed on the FID side. The sample is injected at 40°C. This temperature is held for 2 minutes before ramping at 25°C/min to 245°C followed by another hold period. All products elute within 20 minutes. Total turnaround for the analysis is 30 minutes.

It has been suggested that the acidity of the γ -Al₂O₃ membrane is responsible for the complete plugging of the membrane that you observe. Obviously acid sites will crack hydrocarbons at these temperatures leading to carbonaceous deposits. However, this contribution will diminish once the sites are deactivated by the first monolayer of carbon. Continued deposition should be controllable by adjusting the operating parameters of the reactor.

In our system, we feed the thermosyphon vaporizers with syringe pumps. Steady ethylbenzene and water vapor flows are drawn from the tops of these vaporizers and fed into the reactor. Vapor flowrates are adjusted by use of needle valves and varying vaporizer temperature. Ethylbenzene flows are set to achieve 0.4 hr⁻¹ LHSV and the water/ethylbenzene ratio is targeted for 9. The reactor is heated to temperature in N₂ while the feed flow is stabilized in the reactor bypass before introducing feed to the reactor. Temperatures from 520°C to 600°C have been studied. In particular, we have operated continuously at 600°C for over one week. During the initial startup we observe a steady decline in membrane permeability from approximately 70 m³/m²/hr/atm for the fresh membrane to approximately 2 m³/m²/hr/atm. The permeability stabilizes there as the dynamic equilibrium between carbon deposition and removal is established. We have removed this membrane from the reactor and are currently performing pore size and gas separation characterization on it. Following the initial stabilization of a fresh load of catalyst, we see no major activation or deactivation of the catalyst for run lengths of up to two weeks.

Regarding the University of Wisconsin system, I believe the most important items to address are the method used to introduce liquid feeds to the system and the flowrates being utilized. The peristaltic pumps could probably be retained if a different vaporizer design was used to buffer the fluctuations that come from these types of pumps. Also, operating closer to the target space velocity range should improve coking control. Overall reactor operation could be improved by shifting the thermocouples at the inlet and exit of the reactor into the catalyst bed. A multipoint thermocouple to generate more detailed information on the temperature profile would be even better. Stabilizing the feed flowrate in a bypass loop and exposing the catalyst and membrane to only the final mixture should help minimize the large swings in catalyst activity that Fernando mentioned. A change in the TCD side column and ramping to a higher final temperature on the gc should improve the quality of the analytical results.

I hope this has been helpful. If there is anything else I can do, please feel free to call me.

Sincerely,

END

**DATE
FILMED**

8 / 25 / 92