Novel Nanodispersed Coal Liquefaction Catalysts: Molecular Design Via Microemulsion- Based Synthesis

Technical Progress Report

April - June 1991

by

K. Osseo-Asare and L. R. Radovic

Department of Materials Science and Engineering
The Pennsylvania State University
University Park, PA 16802

Date Published, July 1991

Prepared for the United States
Department of Energy
Under
Contract No. DE-AC22-90PC90054

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

RECEIVED
DOE/PC
JUL 12 1991
U.S. DEPT. OF ENERGY

js2

**Novel Nanodispersed Coal Liquefaction Catalysts:
Molecular Design Via Microemulsion-Based Synthesis**

Technical Progress Report

April - June 1991

by

K. Osseo-Asare and L. R. Radovic

**Department of Materials Science and Engineering
The Pennsylvania State University
University Park, PA 16802**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

July 1991

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

TABLE OF CONTENTS

ABSTRACT.....	iv
PROJECT OBJECTIVES.....	1
STATEMENT OF WORK.....	2
DESCRIPTION OF TECHNICAL PROGRESS	6
Task 1.....	6
Task 3.....	16
REFERENCES.....	21

ABSTRACT

Further progress has been made in our understanding of the aqueous chemistry of molybdenum sulfide. This was used in the synthesis of a microemulsion-based molybdenum catalyst. Preliminary liquefaction tests using this catalyst were carried out and the results look promising.

PROJECT OBJECTIVES

The objective of this project is to pursue the development of highly dispersed and inexpensive catalysts for improved coal solubilization and upgrading of coal liquids. A novel study of the synthesis of liquefaction catalysts of nanometer size will be carried out. It is based on the molecular design of reverse micelles (microemulsions). These surfactant-stabilized, metal-bearing microdrops offer unique opportunities for synthesizing very small particles by providing a cage-like effect that limits particle nucleation, growth and agglomeration. The emphasis will be on iron- and molybdenum-based catalysts, but the techniques to be developed should also be generally applicable. The size of these very small and monodispersed particles will be accurately determined both separately and after *in situ* and *ex situ* coal impregnation. The as-prepared nanoparticles as well as the catalyst-impregnated coal or char matrix will be characterized using the following techniques: dynamic light scattering, x-ray diffraction, x-ray photoelectron spectroscopy, scanning and/or transmission electron microscopy, and selective chemisorption. Catalytic activity tests will be conducted under standardized conditions in both hydrogenation and hydrodesulfurization reactions. The effect of particle size of these unsupported catalysts on the product yield and distribution during liquefaction of a bituminous and a subbituminous coal will thus be quantitatively determined.

STATEMENT OF WORK

The following task activities are being carried out under this project.

Task 1: Formulation, Characterization and Synthesis (Catalyst Preparation)

Subtask 1.1: Microemulsion Formulation and Characterization

We shall formulate and characterize suitable microemulsion media wherein the catalyst particles shall be synthesized. Different surface-active agents shall be considered. These shall include ionic and nonionic systems as well as mixtures of surfactants. The use of cosurfactants and additives shall also be investigated. Special emphasis shall be given to the characterization of microemulsions formulated with polynuclear aromatic compounds (model coal liquefaction solvents) as the external nonpolar phase.

The selection of suitable surfactant systems and characterization methods shall be based on well-documented information in the literature. For example, the phase diagrams shall be based on data obtained by accepted titration techniques. At a minimum, we shall use the techniques of steady-state fluorescence spectroscopy, fluorescence lifetime measurements and dynamic light scattering for the determination of microemulsion structural and dynamic properties. Using the fluorescence techniques, the surfactant aggregation numbers and rates of intermicellar exchange shall be

determined. We shall use light scattering techniques to determine the droplet size, polydispersity and intermicellar interactions. In addition, we shall determine the particle size of the nanoparticles produced.

Subtask 1.2: Catalyst Synthesis

In this subtask, the focus shall be on the preparation of Fe and Mo sulfide nanosize particles. The particles shall be synthesized in microemulsion media using the following techniques:

- (a) mixing two microemulsions containing the metal ion (Fe,Mo) and S anion, respectively;
- (b) bubbling H_2S through a microemulsion containing the metal ions;
- (c) solubilizing both the metal ion and the sulfur-bearing reactant in a microemulsion and inducing the reaction by thermal decomposition of the sulfur donor.

Incorporation of the catalyst particles into the coal matrix shall be achieved using both *ex situ* and *in situ* techniques. The *ex situ* techniques shall involve the impregnation of the coal matrix with nanoparticles prepared by one of the routes described in Subtask 1.1. If the solvent used as the external phase in the microemulsion synthesis does not have the desired wetting characteristics, experiments shall be conducted using particles resuspended in a suitable solvent. By *in situ* technique is meant catalyst synthesis and incorporation into the coal matrix in a single step. One of the *in situ* methods shall involve impregnation of a coal with a metal-ion/sulfur-

donor-loaded microemulsion, followed by heat treatment to promote metal sulfide formation. Other *in situ* methods shall be attempted to identify the best technique to obtain a coal matrix incorporating homogeneously distributed nanosize catalyst particles.

Task 2: Catalyst Characterization

A detailed characterization of the catalyst materials produced in Task 1 shall be performed using the following techniques: dynamic light scattering, UV/visible absorption and fluorescence spectroscopies, x-ray diffraction (XRD), x-ray photoelectron spectroscopy (XPS), scanning and/or transmission electron spectroscopy (SEM/TEM), Mössbauer effect spectroscopy (MES), and selective chemisorption.

For particles developed by *ex situ* techniques, particle size and size distribution shall be determined prior to impregnation into the coal matrix. The change in particle size after introducing the particles into the coal matrix shall be determined. The particle size and particle size distribution after *in situ* impregnation shall be determined. In order to better assess the characterization technique, a limited number of experiments shall be performed on catalyst particles impregnated onto the char derived from the parent coal.

Task 3: Catalyst Testing

Liquefaction tests shall be carried out in stainless steel tubing bomb reactors under standard conditions: 275-400 °C, 7 MPa H₂ (cold), 30 min. Both a hydrogen-donor solvent (e.g., tetralin) and a non-donor solvent (e.g., naphthalene) shall be used. The solvent/coal ratio shall be 2/1. For each catalyst developed in Task 1, liquefaction tests shall be conducted on one bituminous and one subbituminous coal. The coals chosen (with the concurrence of the DOE Project Manager) shall have a sufficiently extensive liquefaction database to permit a meaningful evaluation of the catalysts developed in Task 1. If requested by the DOE Project Manager, samples (up to 5 grams) of catalyst or catalyst-impregnated coal will be provided for independent testing.

A limited number of gasification experiments on catalyst-impregnated coal shall be performed to provide a measure of the coal/catalyst interface area. In selected cases, the kinetics of hydrodesulfurization of a model compound shall be determined to provide a relative comparison of the effectiveness of the catalysts developed in Task 1 in coal dissolution vs. liquid upgrading.

DESCRIPTION OF TECHNICAL PROGRESS

Task 1: Catalyst Preparation

1.1 Aqueous Chemistry of Molybdenum Sulfide: pH Dependence

Colloidal particles of molybdenum sulfide have been prepared in aqueous solution using the method reported by Haruta et al. (1984). A basic solution containing $(\text{NH}_4)_2\text{MoO}_4$, thioacetamide and ammonium hydroxide is aged for 18 h under nitrogen at 50-90 °C. Tetrathiomolybdate ions are formed at $\text{pH} < 9$ and precipitate as molybdenum trisulfide when the solution is acidified with sulfuric acid (Prasilova and Burclova, 1972). The dithio- and trithiomolybdate species are converted to molybdenum oxysulfides (Hoffmeister and Glemser, 1960).

The chemistry pertaining to the formation of molybdenum trisulfide is summarized below.

At $\text{pH} = 3-11$ the following thiomolybdates are formed: $\text{MoO}_3\text{S}^{2-}$, $\text{MoO}_2\text{S}_2^{2-}$, MoOS_3^{2-} and MoS_4^{2-} . Yatirajam et al. (1976) have suggested that molybdenum trisulfide precipitation is more complete if all the molybdenum in aqueous solution is in the form of tetrathiomolybdate prior to acidification. Extensive formation of the tetrathiomolybdate ion has been shown to depend on the sulfur-to-molybdenum molar ratio and on the solution pH. In the work by Prasilova and Burclova (1972), it was shown

that the formation of tetrathiomolybdate species is more complete at a pH of 3-9. Thus, to get a more complete precipitation of molybdenum trisulfide, one has to age the solution of ammonium molybdate and thioacetamide at a pH of 9 or below for about 18 h to obtain appreciable amounts of the tetrathiomolybdate ions before acidifying to a pH of 3 or below to precipitate molybdenum trisulfide.

The tetrathiomolybdate species has been prepared by combining equal volumes of 1 M sodium sulfide and 1×10^{-3} M ammonium molybdate solution; the pH of the resulting solution was decreased to 8 by adding 10% sulphuric acid. The reaction time was 18 h. Figure 1 is the uv/visible absorption spectrum of the thiomolybdate species in solution prepared in this laboratory. The uv/visible spectrum of ammonium tetrathiomolybdate solution (Aymonino et al., 1969) obtained from Aldrich is shown in Figure 2. It can be seen from a comparison of Figures 1 and 2 that, although the percent of MoS_4^{2-} species in the product from Aldrich is greater than that in the solution prepared in this laboratory, the commercial thiomolybdate product still contains some dithiomolybdate species. On the basis of Figures 1 and 2, it is expected that the proportion of molybdenum oxysulfides will be greater for the synthesis done with the thiomolybdate solution prepared in this laboratory.

1.2 Particle Synthesis in Microemulsions

The non-ionic surfactant polyoxyethylene nonylphenyl ether (NP-5) was obtained from GAF Chemical Corporation. The anionic surfactant sodium bis(2-ethylhexyl) sulfosuccinate (AOT, Sigma) was used as received. Cyclohexane and decane were obtained from Aldrich and were dried with

Figure 1. Absorption spectrum of 1×10^{-4} M thiomolybdate species in solution (synthesized in this laboratory).

Figure 2. Absorption spectrum of 1×10^{-4} M thiomolybdate species in solution (obtained from Aldrich).

molecular sieves. Ammonium molybdate, ammonium tetrathiomolybdate and sodium sulfide nonahydrate (Aldrich) were used as received.

Molybdenum sulfide nanoparticles have been prepared in the NP-5 cyclohexane and AOT decane microemulsion systems. The following synthesis methods were used.

- (a) Solubilization of 10% sulfuric acid in one microemulsion followed by addition of MoS_4^{2-} (microemulsion plus a second reactant method).
- (b) Mixing two microemulsions containing MoS_4^{2-} and 10% sulfuric acid, respectively.

For method (a) deoxygenation was achieved by bubbling nitrogen gas in an acid solubilized microemulsion for 20 minutes before MoS_4^{2-} was added. In the case of method (b), both microemulsions were deoxygenated by bubbling nitrogen gas for 20 minutes before mixing.

TEM micrographs of the particles obtained by the microemulsion-plus-a-second-reactant method for the NP-5 cyclohexane microemulsion are shown in Figure 3; the samples were taken 30 minutes after mixing. Also shown in Figure 4 is a plot of the average particle diameter versus the water-to-surfactant molar ratio (R). The particle size increases with the water-to-surfactant molar ratio. This trend is similar to the work reported by Lianos and Thomas (1986), who studied the effect of the water-to-surfactant molar ratio on the size of CdS nanoparticles synthesized in AOT reverse micelles. By varying R from 5 to 32, they found that the particle size increased with R . For a reactant solubilized in an inverse micelle, the term ion occupancy number is defined as the number of reactant species in a given water pool. Molybdenum sulfide will precipitate when the reacting species MoS_4^{2-} and H^+ find themselves in the same inverse micelle. The

Figure 4. A plot of average particle diameter versus water-to-surfactant molar ratio, R. (Synthesis done in the NP-5 cyclohexane microemulsion; concentration of thiomolybdate species, 1×10^{-3} M.)

probability of such an encounter increases as the ion occupancy number is increased.

The process whereby dissolved ions combine to form particles can be represented in the following order: Ions $\rightarrow$ nuclei $\rightarrow$ primary particles. Once a stable nucleus is formed, it can grow by incorporating ions in solution. Although the number of ions in the inverse micelles will increase with R, the number of ions which were not utilized in nuclei formation increases as well. When the ion occupancy number is greater than the number of ions needed to form a critical number of monomers which forms a nucleus, there will be excess ions in the inverse micelles. The excess ions will, therefore, contribute towards growth. Hence, particle size will increase with R.

Figures 5 and 6, respectively, are the absorption spectra of tetrathiomolybdate species and molybdenum sulfide particles in the NP-5 cyclohexane microemulsion. The molybdenum sulfide particles were synthesized by the microemulsion-plus-a-second-reactant method and the sample was taken 1 h after mixing. The two spectra are different in that the absorption peaks for the species MoS_4^{2-} , MoOS_3^{2-} and $\text{MoO}_2\text{S}_2^{2-}$ are absent in Figure 6, and a peak with an onset wavelength of about 350 nm appears. The disappearance of the thiomolybdate peaks suggests that the following conversions took place:

Figure 7 presents the effect of the water-to-surfactant molar ratio (R) on the uv/visible absorption spectra of molybdenum sulfide particles in the

Figure 5. Absorption spectrum of thiomolybdate species in NP-5 cyclohexane microemulsion. ($R=6$, $[\text{Mo}] = 1 \times 10^{-3} \text{ M}$; ammonium tetrathiomolybdate obtained from Aldrich.)

Figure 6. Absorption spectrum of molybdenum sulfide in NP-5 cyclohexane microemulsion. ($R=6$, $[\text{Mo}] = 1 \times 10^{-3} \text{ M}$; ammonium tetrathiomolybdate obtained from Aldrich.)

NP-5 cyclohexane microemulsion. The microemulsion-plus-a-second-reactant method was used for R values of 2-12 and samples were taken 30 minutes after mixing. The onset wavelength shifts to higher wavelengths with increasing R values. This finding is similar to that reported by Lianos and Thomas (1986) for CdS in AOT microemulsions. Figure 8 shows the absorption spectra of molybdenum sulfide particles in the AOT decane microemulsion using the two-microemulsion method; the samples were taken 1 h after mixing. The trend observed is similar to that in the NP-5 cyclohexane microemulsion. The onset wavelength gradually shifts to higher values as R increases.

When a semiconductor absorbs a quantum of light, there is promotion of an electron from an occupied valence band to an unoccupied conduction band. As a result, a hole is created in the valence band. With decreasing particle size, there is an increase in the difference in energy levels between the conduction and the valence bands (Henglein, 1987). As a result, the optical properties, as well as the photocatalytic properties of the particles, change. Thus the gradual shift of the onset wavelength with R, as shown in Figures 7 and 8, implies changes in particle size and hence changes in optical and (photo)catalytic properties of the particles.

1.3 Instrumentation

A dynamic light scattering experimental system, which was ordered from Malvern Instruments (Photon correlation instrument system 4700PS/MW), has been set up, for the most part. The main components of the system are; (a) variable angle spectrometer goniometer, (b) multi-bit correlator, (c) dedicated computer, (d) operating and size analyzing software, (e) laser

Figure 7. Absorption spectra of molybdenum sulfide in NP-5 cyclohexane microemulsion. ($R=2-12$, $[Mo] = 1 \times 10^{-3}$ M; ammonium tetrathiomolybdate obtained from Aldrich.)

Figure 8. Absorption spectra of molybdenum sulfide in AOT decane microemulsion. ($R=2-8$, $[Mo] = 1 \times 10^{-3}$ M; ammonium tetrathiomolybdate obtained from Aldrich.)

light source and a laser table. Its use requires a heat exchanger, and we are in the process of acquiring one.

Task 3: Catalyst Testing

3.1.1 Molybdenum Catalyst Preparation

The method of catalyst impregnation was chosen to take advantage of the positively charged anchoring sites on the coal surface (Solar et al., 1990). The sample used was a Wyodak subbituminous B coal (PSOC 1401). The coal was ground to 200x270 mesh particle size. The catalyst precursor used was ammonium heptamolybdate (AHM). The necessary amount for preparing 1% (wt.) Mo (0.07 g) was dissolved in deionized water. The pH of this solution was adjusted to 2.5, using formic acid. Five grams of coal were then added and the mixture was stirred overnight at 60 °C. The mixture was then dried under vacuum at room temperature for 48 hours.

3.1.2 Iron Catalyst Preparation

The method of catalyst impregnation was chosen to take advantage of the negatively charged anchoring sites on the coal surface (Solar et al., 1990). A sample of the same coal as in 3.1.1 was used. The catalyst precursor was iron nitrate ($\text{Fe}(\text{NO}_3)_2$). The necessary amount for preparing 1% (wt.) Fe (0.5 g) was dissolved in deionized water. The pH of this solution was then adjusted to 10, using ammonium hydroxide. Five grams of coal were added

and the mixture was stirred overnight at 60 °C. The mixture was then dried under vacuum at room temperature for 48 hours.

3.1.3 Microemulsion Catalyst Preparation

A microemulsion prepared in Task 1 was added to 2.5 grams of coal and 5 grams of tetralin. For sample #4, the microemulsion was simply poured into the reactor together with the coal/tetralin slurry. For sample #8, coal, tetralin and the microemulsion catalyst (see Table 3) were stirred magnetically for 18 h prior to the liquefaction experiment (see below).

3.2 Coal Liquefaction Experiments

Samples of the catalyst-impregnated coal were liquefied following the procedure previously used at Penn State (Derbyshire et al., 1986; Davis et al., 1991). The coal (2.5 g), tetralin (5 g) and carbon disulfide (0.12 and 0.36 g for Mo and Fe, respectively) were charged into a 25 cc tubing bomb reactor. The reactor was sealed and pressurized with hydrogen. It was purged three times and finally pressurized to 1000 psig. It was then immersed into a preheated fluidized sand bath at 350 °C, and agitated vertically at a rate of 200 cycles/min and an amplitude of 2.5 cm. The reaction temperature was maintained at 350 ± 2 °C. After 30 minutes of reaction, the reactor was removed and quenched in cold water. The tubing bomb was vented, opened and rinsed with hexane into a weighed ceramic thimble. The reaction products were extracted with hexane in a Soxhlet extractor assembly for 12-18 h, until the solvent falling back into the flask was absolutely colorless.

The hexane was removed in a rotary vacuum evaporator and the product left behind (referred to as oils) was weighed and stored in a vial for GC analysis. The thimble with the residue was dried, weighed and stored in a vial. The product yield was calculated using these weights. The results of the experiments carried out with the Mo and Fe catalysts are listed in Tables 1 and 2, respectively. In each case, three sets of experiments were carried out to test the effect of coal's surface chemistry on catalyst dispersion (and activity). In the first experiment, the catalyst precursor was added and the pH was adjusted as described above; in the second, the catalyst precursor was added without adjusting the pH. The third experiment was a blank test, with no catalyst added.

Similar experiments were carried out using the microemulsion catalyst, and the results are shown in Table 3.

In the above eight experiments, it is assumed that coal undergoes the following reaction:

The yield of oils was calculated in each case as follows (without differentiating asphaltenes and preasphaltenes in the residue):

$$\% \text{ Oils (+ Gas)} = \frac{\text{hexane solubles}}{\text{dmmf coal}} * 100$$

$$\% \text{ Residue} = 100 - \% \text{ Oils}$$

Table 1
Results of Liquefaction Tests Using Mo-Catalyst

Run #	Sample	Catalyst Loading	Yield of Oils (+gas), %	% Residue
1	Coal/Catalyst (pH=2.5)	1.0 % Mo	71.1	28.9
2	Coal/Catalyst	1.0 % Mo	70.2	29.8
3	Coal (no catalyst)	-	29.1	70.9

Table 2
Results of Liquefaction Tests Using Fe-Catalyst

Run #	Sample	Catalyst Loading	Yield of Oils (+gas), %	% Residue
5	Coal/Catalyst (pH=10)	1.0 % Fe	78.8	21.2
6	Coal/Catalyst	1.0 % Fe	74.5	25.5
7	Coal (no catalyst)	-	30.8	69.2

Table 3
Preliminary Results of Liquefaction Tests Using Microemulsion Catalyst

Run #	Sample	Mo Loading	Yield of Oils (+gas), %	% Residue
4	Coal/Mo microemulsion	1.2 ppm	33.8	66.2
8	Coal/Mo microemulsion	2.6 ppm	47.9	52.1

3.3 Discussion of Results

Tables 1 and 2 show that the control of pH during catalyst impregnation had little influence on the yield of oils. The yield is, of course, greatly enhanced in the presence of the catalysts. Of particular interest are the preliminary results using the microemulsion Mo-catalyst (Table 3). With only ppm amounts of Mo, the yield of oils is significantly higher than in the absence of catalyst.

REFERENCES

- Aymonino, P.J., Ranade, A.C., Diemann, E. and Muller, A., *Z. Anorg. Chem.* **371**, 295 (1969).
- Davis, A., Mitchell, G.D., Derbyshire, F.J., Schobert, H.H. and Lin, R., *ACS Preprints (Div. Fuel Chem.)* **36** (2), 445 (1991).
- Derbyshire, F.J., Davis, A., Epstein, M.J. and Stansberry, P.G., *Fuel* **65**, 1233 (1986).
- Haruta, M., Lemaitre, J., Delannay, F. and Delmon, B., *J. Coll. Interf. Sci.* **101**, 59 (1984).
- Henglein, A. *Prog. Coll. Polym. Sci.* **73** 1 (1987).
- Hoffmeister, H.K. and Glemser, O. *Angew. Chem.* **72**, 584 (1960)
- Lianos, P. and Thomas, J.K., *Chem. Phys. Lett.* **125**, 299 (1986).
- Prasilova, J. and Burclova, J., *Radiochem. Radioanal. Lett.* **11**, 351 (1972).
- Solar, J.M., Leon y Leon, C.A., Osseo-Asare, K. and Radovic, L.R., *Carbon* **28**, 369 (1990).
- Yatirajam, V., Ahuja, U. and Kakkar, L.R., *Talanta* **23**, 819 (1976).

**DATE
FILMED
8/10/92**