**Development of An Advanced, Continuous Mild Gasification
Process for the Production of Co-Products (Task 1),
Volume I**

Final Report

**R.A. Knight
J.L. Gissy
M. Onischak
S.P. Babu
R.H. Carty
R.G. Duthie (Bechtel Group, Inc.)
J.M. Wootten (Peabody Holding Co. Inc.)**

September 1991

Work Performed Under Contract No.: DE-AC21-87MC24266

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
Morgantown, West Virginia**

**By
Institute of Gas Technology
Chicago, Illinois**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, ~~1-800-553-6044~~.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Development of An Advanced, Continuous Mild Gasification
Process for the Production of Co-Products (Task 1),
Volume I**

Final Report

**R.A. Knight
J.L. Gissy
M. Onischak
S.P. Babu
R.H. Carty
R.G. Duthie (Bechtel Group, Inc.)
J.M. Wootten (Peabody Holding Co. Inc.)**

Work Performed Under Contract No.: DE-AC21-87MC24266

**For
U.S. Department of Energy
Office of Fossil Energy
Morgantown Energy Technology Center
P.O. Box 880
Morgantown, West Virginia 26507-0880**

**By
Institute of Gas Technology
IIT Center, 3424 S. State Street
Chicago, Illinois 60616**

September 1991

Volume I

Project Summary

Literature Survey of Mild Gasification Processes,
Co-Product Upgrading and Utilization, and Market
Assessment (Program Task 1)

Volume II

Mild Gasification Technology Development:
Process Research Unit Tests Using Slipstream Sampling
(Program Task 2)

Bench-Scale Char Upgrading Study
(Program Task 3)

Mild Gasification Technology Development:
System Integration Studies
(Program Tasks 4.1 to 4.6)

Volume III

Mild Gasification Technology Development:
24 Ton Per Day Process Development Unit Design
and Cost Estimates (Program Task 4.7)

TABLE OF CONTENTS

	<u>Page</u>
PROJECT GOALS	I-1
APPROACH	I-2
TASK 1. LITERATURE SURVEY AND MARKET ASSESSMENT	I-4
Subtask 1.1. Literature Survey of Mild Gasification Processes	I-4
Objective	I-4
Introduction	I-4
Effect of Operating Conditions on Devolatilization Characteristics of Coal	I-5
Effect of Coal Type	I-5
Effect of Temperature	I-11
Effect of Pressure	I-21
Effect of Reactive Gas Composition	I-25
Effect of Particle Heating Rate	I-30
Effect of Particle Size	I-33
Effect of Sulfur-Capture Additives	I-33
Effect of Coal Pretreatment	I-35
Summary of the Effects of Operating Conditions	I-35
Review of Carbonization Processes That Meet the Criteria of Mild Gasification	I-37
Fixed-Bed Processes	I-37
Moving-Bed Processes	I-39
Fluidized-Bed Processes	I-69
Entrained-Bed Processes	I-75
Summary of Published Process Data With Emphasis on Bituminous Coal Product Yields and Quality	I-83
Comparison to Oil Shale Conversion Processes	I-88
Conclusions Leading to the Selection of a Range of Operating Conditions and Reactor Design Criteria	I-90
Subtask 1.2. Literature Survey of Char, Condensables, and Gas Upgrading and Utilization Methods	I-95
Objective	I-95
Char Upgrading Methods	I-95
Char Properties and Product Specifications	I-95
Conventional Upgrading Technologies	I-98

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Gravity Separation Methods	I-98
Flotation	I-98
Advanced Upgrading Technologies	I-99
Selective Agglomeration	I-99
Advanced Dense-Medium Separation	I-100
Advanced Flotation	I-101
Selective Flocculation	I-102
Electrostatic Separation	I-104
High Gradient Magnetic Separation	I-104
Chemical Coal Cleaning	I-104
Ultra-High Temperature Pyrolysis	I-107
Summary of Char Upgrading Methods	I-107
Char Utilization Methods	I-109
Utility Applications	I-110
Fine Char From Entrained-Bed Mild Gasification	I-110
Coarse Char From Fluidized-Bed Mild Gasification	I-113
Nonutility Applications	I-114
Fine Char From Entrained-Bed Mild Gasification	I-114
Coarse Char From Fluidized-Bed Mild Gasification	I-117
Summary of Char Utilization Methods	I-118
Condensable Hydrocarbons Upgrading Methods	I-119
Properties of Condensable Hydrocarbons	I-119
Coal Tar	I-125
Light Oil	I-125
Liquor	I-125
Conventional Upgrading Technologies in Coal Carbonization	I-125
Conventional Upgrading Technologies in Coal Liquefaction and Petroleum Refining	I-132
Hydrotreating	I-132
Hydrocracking	I-134
Catalytic Cracking	I-135
Steam Cracking	I-136
Reforming	I-136
Other Upgrading Methods	I-138

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Summary of Condensable Hydrocarbons Upgrading Methods	I-138
Condensables Utilization Methods	I-139
Fuel Applications	I-139
Gasoline	I-141
Diesel Fuel	I-141
Fuel Oil	I-141
High-Density Fuel	I-143
Nonfuel Applications	I-143
Phenol, Cresols, and Xylenols (PCX)	I-143
Benzene, Toluene, and Xylenes (BTX)	I-144
Naphthalene	I-145
Creosote and Creosote Oils	I-145
Pyridine Bases	I-146
Indene-Coumarone Resins	I-146
Medium-Soft Pitch	I-146
Medium-Hard Pitch	I-147
Summary of Condensables Utilization Methods	I-147
Fuel Gas Upgrading Methods	I-149
Properties of Fuel Gas	I-149
Upgrading Technologies	I-149
Ammonia Removal and Recovery	I-149
Sulfur Gas Removal and Recovery	I-150
Light Gas Separation	I-150
Synthesis Gas	I-150
Summary of Fuel Gas Upgrading Methods	I-150
Fuel Gas Utilization Methods	I-151
Fuel Applications	I-151
Industrial Fuel Gas	I-151
Methanol Synthesis for Fuel	I-152
Nonfuel Applications	I-152
Hydrogen	I-152
Synthesis for Chemicals	I-152
Summary of Fuel Gas Utilization Methods	I-152

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Co-products Upgrading Methods for Selected End Uses	I-153
Char Uses	I-153
Combustion	I-153
Metallurgical Uses	I-153
Active Char	I-153
Char Gasification	I-154
Domestic Fuel Use	I-154
Condensable Hydrocarbons Uses	I-154
Chemical Feedstocks	I-155
Octane Enhancers	I-155
Preservatives	I-155
Binders	I-155
Fillers	I-156
Fuel Gas Uses	I-156
Onsite Combustion	I-156
Ammonia Synthesis	I-156
Conclusions Leading to the Selection of Co-products Upgrading Methods	I-157
Subtask 1.3. Market Assessment	I-159
Objective	I-159
Introduction	I-159
Market Assessment of Solid Co-products	I-160
Char/Coal Utility Fuel	I-160
Utility Bituminous Coal Consumption	I-161
Coal Supply Agreement Specifications	I-163
Modes of Transportation	I-164
Char Quality	I-164
Market Acceptance	I-164
Marketing Strategy	I-171
Form Coke	I-176
Status of the American Steel Industry	I-176
Form Coke Processes	I-181
Coke Prices	I-184
Marketing Strategy	I-185

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Smokeless Domestic Fuel or District Heating Fuel	I-185
Adsorbent Carbon or Char	I-187
Market Assessment of Condensable Hydrocarbons	I-189
Tar Pitch	I-190
Heavy Creosote Oil	I-192
Carbon Black	I-192
Middle Oils	I-193
Light Oils	I-193
Ammonium Sulfate	I-194
Marketing Strategy	I-194
Conclusions From Market Assessment of Solid and Condensable Co-products	I-195
DISCUSSION OF MILD GASIFICATION TECHNOLOGY	I-197
Mild Gasification Reactor Systems	I-197
Fixed-Bed Reactor	I-197
Vertical Moving-Bed Reactor	I-197
Horizontal Moving-Bed Reactor	I-199
Conveyor-Bed Reactor	I-199
Fluidized-Bed Reactor	I-199
Entrained-Bed Reactor	I-200
Selection of a Reactor Design	I-200
Conceptual Advanced Mild Gasification Process Schemes	I-207
Option I. Char/Coal Blending for Utility Fuel	I-209
Size Reduction	I-209
Coal Cleaning	I-209
Dewatering/Screening	I-211
Dryer/Preheater	I-211
Mild Gasification	I-211
Solids Disengagement	I-211
Char Blending	I-212
Spray Coolers	I-212
Decanter	I-213
Saturator	I-213

TABLE OF CONTENTS, Cont.

	<u>Page</u>
Ammonia Still/Extraction	I-213
Recirculating Oil Scrubber	I-213
Steam Strippers	I-214
Tar Fractionation	I-214
Pitch Cracking	I-214
Option II. Metallurgical Form Coke Production	I-215
Form Coking	I-215
Option III. Smokeless Domestic Fuel Production	I-215
Briquetting	I-218
Revenue Potential for the Selected Process Schemes	I-218
Process Commercialization Plan	I-222
Timetable for Commercial Development	I-224
Market Penetration Potential	I-225
Institutional Barriers	I-225
Infrastructure for Transportation and Distribution	I-226
Availability of Manufacturing Infrastructure	I-226
TECHNOLOGY DEVELOPMENT RECOMMENDATIONS	I-227
Task 2. Bench-Scale Mild Gasification Study	I-227
Scope	I-227
Purpose	I-227
Discussion	I-228
Task 3. Bench-Scale Char Upgrading Study	I-228
Scope	I-228
Purpose	I-229
Discussion	I-229
REFERENCES CITED	I-232
APPENDIX A. Summary of Oil Shale Processing	I-A-1
APPENDIX B. Detailed Information on Sources and References Used for Market Assessment	I-B-1
APPENDIX C. Discussion of Other Potential Markets for Coal-Derived Co-products	I-C-1

TABLE OF CONTENTS, Cont.

	<u>Page</u>
APPENDIX D. Typical Coal Quality	I-D-1
APPENDIX E. Market Survey for Reduced-Sulfur Coal	I-E-1
APPENDIX F. Adjustments to Fuel Cost and Premium/Penalty Calculation Procedures	I-F-1
APPENDIX G. Description of Form Coke Processes	I-G-1

LIST OF FIGURES

<u>Figure No.</u>		<u>Page</u>
I-1	Yield and Distribution of Devolatilization Products for Three Bituminous Coals and One Lignite	I-6
I-2	Comparison of Devolatilization Yields for Three Low-Rank Coals and Pittsburgh Seam Coal	I-7
I-3	Tar Yields for Five High-Rank Coals Under Nitrogen at Varying Pressures and Heating Rates	I-8
I-4	Variation in Devolatilization Yields at 1112°F With H/C Atomic Ratio of Coal	I-9
I-5	Effect of Coal Type on Devolatilization Product Gas Yields	I-10
I-6	Elemental Composition of Coal Chars Carbonized at Different Temperatures and Particle Residence Times	I-13
I-7	Elemental Compositions of Coal Chars Devolatilized in a Crucible at Temperatures From 400° to 2000°C	I-14
I-8	Nitrogen Concentration in Devolatilization Products at Various Temperatures	I-15
I-9	Conversion of Coal Sulfur to H ₂ S for the Devolatilization of Three Bituminous Coals	I-16
I-10	Devolatilization Product Distribution, Including H ₂ S, for Coal Heated to Various Temperatures	I-18
I-11	Evolution of Gases From Devolatilization of Bituminous Coal as a Function of Temperature	I-19
I-12	Comparison of Coal Nitrogen in Tar With Tar Yield	I-22
I-13	Char Volatile Matter Relative to Coal Volatile Matter as a Function of Temperature for Three Types of Carbonization Processes	I-24
I-14	Effect of Helium Pressure on Tar Yield From Pittsburgh Seam Coal at Various Devolatilization Temperatures	I-26
I-15	Effect of Sub-atmospheric Helium Pressure on Product Yields From Devolatilization of Pittsburgh Seam Coal	I-27
I-16	Effect of Hydrogen Pressure on Coal Conversion	I-28
I-17	Photomicrograph of Coal Chars Produced by Carbonization at Various Heating Rates	I-34

LIST OF FIGURES, Cont.

<u>Figure No.</u>		<u>Page</u>
I-18	Devolatilization Yields From Steam-Treated and Untreated Bituminous Coal	I-36
I-19	Cross-Section View of Phurnacite Retort	I-40
I-20	Cross-Section View of Cellan-Jones Retort	I-41
I-21	Rexco Low-Temperature Carbonization Process Schemes	I-42
I-22	Cross-Section Views of Krupp-Lurgi Retort	I-43
I-23	Cross-Section View of Curran-Knowles Retort	I-44
I-24	Cross-Section View of Coalene Retort	I-45
I-25	Layout of UCC Retort System	I-46
I-26	Cross-Section View of Brennstoff-Technik Retort	I-47
I-27	Layout of Otto and Weber Low-Temperature Carbonization Plant	I-48
I-28	Cross-Section View of Carmaux Retort	I-49
I-29	Schematic Diagram of Lurgi-Spülgas Low-Temperature Carbonization Plant	I-50
I-30	Cross-Section View of Koppers Moving-Bed Low-Temperature Carbonization Reactor	I-51
I-31	Cross-Section View of Borsig-Geissen Moving-Bed Low-Temperature Carbonization Reactor	I-52
I-32	Cross-Section View of Didier-Werke Moving-Bed Low-Temperature Carbonization Reactor	I-53
I-33	Schematic Diagram of Koal Krudes Low-Temperature Carbonization Plant	I-54
I-34	Schematic Diagram of National Fuels Moving-Bed Low-Temperature Carbonization Reactor	I-55
I-35	Schematic Diagram of Heliopore Moving-Bed Low-Temperature Carbonization Reactor	I-56
I-36	Cross-Section View of Petit Moving-Bed Low-Temperature Carbonization Reactor	I-57
I-37	Cross-Section View of Pintsch-Weber Moving-Bed Low-Temperature Carbonization Reactor	I-58

LIST OF FIGURES, Cont.

<u>Figure No.</u>		<u>Page</u>
I-38	Cross-Section View of Stansfield Moving-Bed Low-Temperature Carbonization Reactor	I-59
I-39	Cross-Section View of Disco Moving-Bed Low-Temperature Carbonization Reactor	I-61
I-40	Cross-Section View of Mimura Moving-Bed Low-Temperature Carbonization Reactor	I-62
I-41	Schematic Diagram of Lurgi-Ruhrgas Low-Temperature Carbonization Plant	I-63
I-42	Cross-Section View of Hayes Moving-Bed Low-Temperature Carbonization Reactor	I-64
I-43	Schematic Diagram of Toscoal Low-Temperature Carbonization Plant	I-65
I-44	Cross-Section View of Storrs Moving-Bed Low-Temperature Carbonization Reactor	I-66
I-45	Schematic Diagram of Dravo Straight-Grate Low-Temperature Carbonization Process	I-67
I-46	Layout of Flat-Bed Low-Temperature Carbonization Reactor	I-68
I-47	Schematic Diagram of COED Fluidized-Bed Coal Carbonization Process	I-70
I-48	Schematic Diagram of Seacoke Co-Carbonization Process	I-71
I-49	Schematic Diagram of FMC Coke Process	I-72
I-50	Schematic Diagram of Consol Fluidized-Bed Low-Temperature Carbonization Process	I-73
I-51	Schematic Diagram of Singh Fluidized-Bed Low-Temperature Carbonization Process	I-74
I-52	Schematic Diagram of United Engineers Fluidized-Bed Low-Temperature Carbonization Process	I-76
I-53	Schematic Diagram of Southern Research Institute Fluidized-Bed Process	I-77
I-54	Cross-Section and Schematic Diagram of CERCHAR Fluidized-Bed Process	I-78
I-55	Schematic Diagram of CSIRO Fluidized-Bed Process	I-79

LIST OF FIGURES, Cont.

<u>Figure No.</u>		<u>Page</u>
I-56	Schematic Diagram of Occidental Research Corporation Entrained-Bed Bench-Scale Reactor	I-80
I-57	Schematic Diagram of Occidental Research Corporation Flash Pyrolysis Pilot Plant	I-81
I-58	Cross-Section View of Parry Entrained-Bed Low-Temperature Carbonization Reactor	I-82
I-59	Char Yields From Bituminous Coals vs. Temperature for Fixed-Bed, Moving-Bed, Fluidized-Bed, and Entrained-Bed Carbonization	I-84
I-60	Progression of Carbonaceous Matter From Coal Oil to Graphite	I-85
I-61	Tar/Oil Yields From Carbonization of Bituminous Coals in Fixed, Moving, Fluidized, and Entrained Beds	I-87
I-62	Product Gas Heating Value as a Function of Temperature for Coal Carbonization in Externally Heated Fixed, Moving, and Fluidized Beds	I-89
I-63	Advanced Feed Coal Cleaning Concept for Ash and Mineral Sulfur Reduction	I-108
I-64	Use of Entrained-Bed Char for Power Generation	I-111
I-65	Use of Fluidized-Bed Char for Power Generation	I-112
I-66	Nonutility Applications for Char From Entrained Bed Mild Gasification	I-115
I-67	Nonutility Applications for Char From Fluidized Bed Mild Gasification	I-116
I-68	Sulfur Contents of Coal and COED Oil	I-121
I-69	Nitrogen Contents of Coal and COED Oil	I-122
I-70	Oxygen Contents of Coal and COED Oil	I-123
I-71	Coal By-product Tree	I-126
I-72	Schematic Drawing of a Typical Coke-Oven By-product Recovery System	I-127
I-73	Schematic Drawing of a Typical Coal Tar Distillation Plant (Teerverwertung-Koppers)	I-129

LIST OF FIGURES, Cont.

<u>Figure No.</u>		<u>Page</u>
I-74	Distillation Curves for Feed and Products of COED Oil	I-133
I-75	Schematic Drawing of ARCO Program for Upgrading COED Liquids	I-140
I-76	Integrated Coal Preparation and Mild Gasification Process Material Flows	I-174
I-77	Projected Supply of Metallurgical Coke From Domestic Coke Ovens and Imports	I-180
I-78	Comparison of Domestic Fuel Price	I-188
I-79	Coal Tar Production Trends in the United States From 1965 to 1984	I-191
I-80	Projected Mild Gasification Reactor Performance	I-203
I-81	Schematic Drawing of Proposed Mild Gasification Reactor	I-206
I-82	Illustrative Integrated Process	I-208
I-83	Option I: Process Scheme for Char/Coal Blending for Utility Fuel Production and Tar Fractionation	I-210
I-84	Option II: Process Scheme for Metallurgical Form Coke Production and Tar Fractionation	I-216
I-85	Option III: Process Scheme for Smokeless Fuel Production and Tar Fractionation	I-217
I-86	Process Options -- Distribution of Plant Investment	I-220

LIST OF TABLES

<u>Table No.</u>		<u>Page</u>
I-1	Comparison of Coals of Different Ranks and Their Liquid Products	I-11
I-2	Comparison of Sulfur Content in Tars for Three Low-Temperature Carbonization Processes	I-17
I-3	Comparison of Occidental Flash Pyrolysis Tars From Bituminous Coal With Two Different Heat Carriers	I-20
I-4	Comparison of Light Oil Components From Low-, Medium-, and High-Temperature Carbonization	I-21
I-5	Comparison of Condensable Devolatilization Product Compositions From Coke Ovens (~1800°F), CVR Retorts (~1500°F), and Low-Temperature Retorts (~1200°F)	I-23
I-6	Properties of Flash Pyrolysis Tars Produced at Different Operating Conditions	I-29
I-7	Properties of Condensables From Rapid and Slow Heating Rate Devolatilization of Utah hvb Coal	I-31
I-8	Product Distribution From Rapid and Slow Heating Rate Devolatilization of German Bituminous Coal	I-31
I-9	Composition of Condensable Products From Rapid and Slow Heating Rate Devolatilization of German Bituminous Coal	I-32
I-10	Reactor Configurations, Operating Conditions, and Product Yields From Low-Temperature, Low-Pressure Carbonization Processes	I-38
I-11	Comparison of Typical Condensables From Coalite and Occidental Flash Pyrolysis	I-91
I-12	Chars From Mild Gasification of Midwestern Coals	I-96
I-13	Characteristics of Blast Furnace Coke	I-97
I-14	Coal Cleaning Processes: Process Conditions and Illustrative Performance	I-106
I-15	Comparison of COED Feed Coals and Condensables Produced	I-120
I-16	Comparison of an Indian Coal Liquid and Petroleum Crude	I-120
I-17	Typical Distillation Cuts From Coke-Oven, Continuous Vertical Retort, and Low-Temperature Retort Tars	I-124
I-18	Constituents of Coal Tars From Various Sources	I-131

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
I-19	Comparison of Results of Hydrotreating With Hydrocracking of a Coal-Derived Liquid	I-135
I-20	Catalytic Cracking of a Coal Oil	I-136
I-21	Steam Cracking of Various Hydrocarbon Liquids	I-137
I-22	Characteristics of Coal Condensables and Other Liquid Fuels	I-142
I-23	Polymers That Use Phenolic Chemicals in Their Manufacture	I-144
I-24	Typical Product Gas Composition From Mild Gasification of a High-Volatile Bituminous Coal in Nitrogen	I-149
I-25	Projections of U.S. Coal Consumption	I-161
I-26	Delivered Quantity, Quality, and Cost of High-Sulfur, High-Volatile Bituminous Coal for the Period January Through July 1987	I-162
I-27	Survey of Major Coal Supply Agreement Specifications	I-163
I-28	Domestic Distribution of U.S. Coal by Origin, Method of Transportation and Consumer: January Through June 1987	I-165
I-29	Analysis of Second- and Third-Stage FMC COED Char	I-166
I-30	Properties of Coals and Mild Gasification Chars From Illinois No. 6 and Pittsburgh No. 8 Coals	I-167
I-31	Summary of Char Market Survey Results	I-169
I-32	Preparation Plant Product Quality	I-173
I-33	Product Coal Size Distribution	I-175
I-34	Coal and Char Quality and Price for Illinois No. 6 Coal	I-175
I-35	World Pig Iron Production Statistics	I-177
I-36	U.S. Consumption of Metallurgical Coke	I-178
I-37	Age Profile of U.S. Coke Ovens as of December 31, 1987	I-178
I-38	Pertinent Features of Various Form Coke Processes	I-182
I-39	U.S. Production of Selected Co-products	I-193

LIST OF TABLES, Cont.

<u>Table No.</u>		<u>Page</u>
I-40	Comparison of Condensable Hydrocarbon Yields From One Integrated Mild Gasification Plant With Most Recent U.S. Production	I-194
I-41	Comparison of Conceptual Mild Gasification Reactor Types	I-198
I-42	Total Capital Requirements for Selected Char Utilization Options	I-219
I-43	Annual Operating Costs and Product Credits for Selected Process Options	I-221
I-44	Economic Summary of Three Mild Gasification Process Options	I-222
I-45	Commercialization Timetable	I-224

20WP/61089pre/RPP

PROJECT SUMMARY

Introduction and Background

Under U.S. DOE sponsorship, a project team consisting of the Institute of Gas Technology, Peabody Holding Company, and Bechtel Group, Inc. has been developing an advanced, mild gasification process to process all types of coal and to produce solid and condensable liquid co-products that can open new markets for coal. The three and a half year program (September 1987 to June 1991) consisted of investigations in four main areas. These areas are:

- Literature Survey of Mild Gasification Processes, Co-Product Upgrading and Utilization, and Market Assessment
- Mild Gasification Technology Development: Process Research Unit Tests Using Slipstream Sampling
- Bench-Scale Char Upgrading Study
- Mild Gasification Technology Development: System Integration Studies

The project was initiated with a literature survey and market assessment to identify an advanced gasifier design to produce the most marketable co-products. Following this effort, a 100 pound per hour process research unit was designed, built, and operated to evaluate the process concept and to obtain parametric test data on various coals, namely an Illinois No. 6, a West Virginia metallurgical coal, and a western sub-bituminous coal. Briquettes of the chars were made for evaluation as blast furnace coke, as a smokeless fuel, and as an adsorbent char carbon.

As part of the System Integration Studies, a 24-ton per day process development unit was designed on the basis of the data obtained in the process research unit. An associated 24-ton per day hot briquetting system was also designed to make form coke from the mild gasification chars. The intended site for the process development unit is at the Illinois Coal Development Park in Carterville, Illinois operated by Southern Illinois University at Carbondale. The final report of the project work is divided into three volumes.

Volume I Project Summary

Literature Survey of Mild
Gasification Processes, Co-Product Upgrading and
Utilization, and Market Assessment (Program Task 1)

Volume II Mild Gasification Technology Development:
Process Research Unit Tests Using Slipstream Sampling
(Program Task 2)

Bench-Scale Char Upgrading Study
(Program Task 3)

Mild Gasification Technology Development:
System Integration Studies
(Program Tasks 4.1-4.6)

Volume III 24 Ton Per Day Process Development Unit Design:
P & ID, Capital and Operating Cost Estimate
(Program Task 4.7)

Results

During the first 4 months of the program, a literature search on the devolatilization of coal, mild coal gasification processes, and upgrading and utilization of the co-products was conducted. A concurrent market survey was conducted to identify the value-added uses for the coal-derived co-products. The resulting priority end uses formed the basis for the selection of a mild gasification reactor system and the co-products handling and upgrading process scheme. A conceptual process flow sheet was developed for a 1 million ton/year mild gasification plant, and a preliminary economic analysis was carried out. During this investigation, the technology development needs for the selected conceptual process were also determined. The results of this work are detailed in Volume I.

The literature review showed that the high-volatile bituminous coals produce the highest yields and most valuable condensable hydrocarbons during mild gasification. The highest condensable yields are obtained in the temperature range of 1100° to 1300°F. Rapid heating, enabled by the use of a small particle size, minimizes secondary condensables' decomposition reactions, thus increasing the yield of valuable condensable hydrocarbons. The literature also showed that lower pressures favor the yield of condensable hydrocarbons. There is some evidence that when steam and CO₂ are used as the mild gasification medium, the deposition and cracking of the condensables on

the surface of char particles may be inhibited, thus improving the production of condensables. Sulfur-capture additives (calcium and iron oxides) may provide catalytically active surfaces for thermally cracking the condensable hydrocarbons and therefore act to decrease tar production. However, these additives have the capability to selectively absorb the H_2S and may even promote the release of sulfur contained in coal.

The concept of integrating the conceptual mild gasification process with the mine-mouth coal preparation plant was analyzed to assess the technoeconomic benefits of utility fuel production. A case was analyzed in which the coal fines from the preparation plant are fed to the mild gasification reactor, and the resulting char is again blended with the preparation plant coal product. Several benefits could be realized from this integration scheme. These benefits include conservation of energy in drying the -1/2-in. size fraction by mixing the hot char with the moist coal stream. In addition, it is possible to reduce the amount of fines when some of the coal passes through the plastic range as it comes in contact with 1200°F char. The excess product fuel gas could also be used to dry the remaining 2-in. x 1/2-in. steam coal product to earn a premium on fuel value. Alternatively, the gas could be used in combined-cycle power generation and char fines combustion employed for coal drying.

An order of magnitude (scoping) capital and operating cost estimate for a million ton/yr conceptual mild gasification plant was prepared using conservatively estimated product costs for the following three char utilization options:

- I. Char blended with coal for utility fuel
- II. Char briquetted with coal fines and then carbonized to metallurgical form coke
- III. Char briquetted with coal fines for use as a smokeless domestic, district-heating, or industrial fuel.

Options II and III for the two char-derived fuels (metallurgical form coke, smokeless fuel briquettes) show potential for attractive return on investment in the 25% to 30% range. Option I for char blending with the preparation plant washed coal products shows a much smaller return. However, this assessment reflects a very conservative evaluation of the char fuel value contribution to the total fuel product. The estimated net operating profit does not include debt service charges, taxes, or facility amortization.

Based on the market and literature survey results, and a review of the most recent experience with gasification of caking high-volatile bituminous coals at IGT and elsewhere, a gasifier consisting of fluidized-bed and entrained-bed stages was selected. The primary reason for selecting a combination of the two gas-solid contacting schemes is to provide optimum reaction conditions for widely differing coal particle sizes and to maximize the yield of value-added condensable hydrocarbons rich in pitch and aromatics.

An isothermal process research unit (PRU) was built at IGT, consisting of an 8-inch-ID, 8-foot-long fluidized-bed section and a 4-inch-ID, 13-foot-long entrained-flow section, externally heated by electrical heaters. The coal feed capacity is 100 lb/h, and the coal can be fed either to the fluidized bed or to the freeboard region above the fluidized bed and below the entrained section. The stainless steel reactor vessel was designed for operation at a maximum temperature and pressure of 1500°F and 50 psig, respectively.

Data analysis from the successful PRU tests with Peabody's Illinois No. 6 and West Virginia coals show that, in the temperature range of 1035° to 1390°F, coal conversion ranged from 24% to 46%, resulting in 54% to 76% char, 13% to 29% oils/tar, and 5% to 19% fuel gas. The test data with the Illinois coal show that increasing reaction temperature increases coal conversion, with decreasing char yield. The oils/tar yields appear to maximize around 1100°F, while the gas yield increases steadily with increasing temperature, primarily due to increasing secondary thermal cracking reactions. The highly aromatic oils and tars were characterized to estimate the light oil (<350°F), middle oil (350° to 590°F), heavy oil (590° to 750°F), and pitch (>750°F) distillation fractions. The predominance of secondary reactions is also evident in the effect of temperature on the amounts of various oils/tars produced. It was determined that with increasing mild gasification temperature, the pitch fraction decreased with a corresponding increase in lighter fractions, particularly the light oil.

The fuel gas from mild gasification is rich in hydrogen and methane and it also contains other light hydrocarbons, carbon oxides, and hydrogen sulfide. Increasing temperature reduces methane and increases hydrogen content, which effects are also attributable to secondary cracking and reforming reactions and to gas-phase C/H/O equilibria.

The char volatile matter content was in the range of 7% to 12%, reduced from the 37% volatile matter content of the dry Illinois No. 6 coal.

Analysis of the fate of sulfur with increasing reaction temperature showed that the sulfur content in char and gases decreased while the sulfur content of oils/tars increased. In general, for Illinois coal, the char contained 36% to 54% of the sulfur, oils and tars contained 9% to 15% of the sulfur, and the fuel gas contained 31% to 52% of the sulfur in the coal.

The chars from the mild gasification PRU and from a laboratory fluidized bed were evaluated with bench-scale performance tests specific for each of the three products. The investigation indicated that a form coke briquette made from metallurgical grade coals can be made of sufficient strength and in the proper range of coke reactivity. Larger scale tests will be required to prove the performance of the form coke in industrial equipment, but the major factors of strength and reactivity should not be a technical barrier.

Briquettes of smokeless fuel do not have to be as strong as the form coke briquettes. Limestone, which can be easily blended into the char briquettes, has been shown to capture 88% of the sulfur from the char of an Illinois No. 6 coal in simple combustion tests. The coal sulfur was found to be completely converted to calcium sulfate in the combusted ash residue.

A good-quality, low-cost activated adsorbent char was prepared from Illinois No. 6 char by optimizing the carbon burn-off with steam. The adsorbent char was comparable in performance characteristics to a commercial bituminous coal-based activated char and was found to be particularly well-suited for adsorption of low-molecular-weight species.

In the PRU tests, the use of recycle char from previous PRU tests mixed with the caking coal feed to the fluidized bed simulated the scale-up adiabatic process development unit (PDU) that will use recycled hot char. Also, one test was performed to evaluate the effect of carbon dioxide in the inlet fluidization gas, as would be present in the PDU design using heated recycled product gas for fluidization.

Co-product yields and quality were compared with previous data and related to sequential char recycle, fluidization gas, and coal type. Oils/tars yields from Illinois and West Virginia bituminous coals were consistently over 25% by weight of maf coal, and were not adversely affected either by

replacement of the coke diluent with mild gasification-derived char or by the use of 19% CO₂ in the fluidization gas. The steady operation of the IGT mild gasification PRU with 100% non-caking coal at 102 lb/h was also demonstrated showing the versatility of the reactor design.

The information obtained in the PRU testing program was used by Bechtel Group, Inc. as a basis for the design of a 24 ton per day mild gasification process development unit (PDU) with an associated hot briquetting system to produce form coke from the mild gasification chars.

Conclusions

An 8-inch-ID, isothermal process research unit (PRU) for the IGT Mild Gasification process has been constructed and operated successfully for 26 steady-state tests, with closed material balances, at coal feed rates up to 100 lb/h. In these tests, several caking eastern coals and a non-caking western coal have been successfully tested. The continuous processing of caking coals in a single reactor has been the major achievement of this program. The PRU has produced char and liquids for bench-scale evaluation. The char has been processed into form coke briquettes on a small scale, and these were tested for strength and density. The liquids were evaluated for fractionation into fuels and chemical feedstocks. The results of these product evaluations have been used in the design of the onsite product upgrading for the PDU.

The 24 ton/day PDU facility is comprised of a 2.5-ft ID adiabatic gasifier for the production of gases, coal liquids, and char; a thermal cracker for upgrading of the coal liquids; a hot briquetting unit for the production of binderless briquettes; and a calciner for producing form coke for blast furnaces and cupolas. These facilities are supported by an incinerator and a scrubber for environmentally acceptable disposal of all process-generated gases and surplus coal liquids.

The intended site for the PDU is at the Illinois Coal Development Park at Carterville, Illinois operated by Southern Illinois University at Carbondale. The design offers flexibility and options for operation in terms of heat supply to the gasifier, a thermal cracking of the liquids before condensation, and a hot briquetting system able to investigate hot binderless briquetting of mild gasification chars with additives and various char/binder-coal mixtures.

VOLUME I. EXECUTIVE SUMMARY

Literature Survey of Mild Gasification Processes, Co-Product Upgrading and Utilization, and Market Assessment (Program Task 1)

The primary objective of the project is to develop an advanced, mild coal gasification process to produce co-products that can open new markets for coal in both the utility and non-utility sectors. A project team was assembled to do this work consisting of the Institute of Gas Technology, an experienced process developer; Peabody Holding Co., representing the largest coal producer in the United States; and Bechtel National, Inc., a worldwide engineering design firm.

This report section summarizes the work done during the first 4 months of the program: a literature search on the devolatilization of coal, mild coal gasification processes, and upgrading and utilization of the co-products. A concurrent market survey was conducted to identify the value-added uses for the coal-derived co-products. The resulting priority end uses formed the basis for the selection of a mild gasification reactor system and the co-products handling and upgrading process scheme. A conceptual process flow sheet was developed for a 1 million ton/year mild gasification plant, and a preliminary economic analysis was carried out. During this investigation, the technology development needs for the selected conceptual process were determined. Upon receiving the Department of Energy's (DOE's) authorization the project team began the experimental and analytical investigations and conceptual design evaluations leading to the generation of process engineering data essential for the scale-up and commercialization of advanced, mild gasification technology.

The literature review showed that the high-volatile bituminous coals produce the highest yields and most valuable condensable hydrocarbons during mild gasification. The highest condensable yields are obtained in the temperature range of 1100° to 1300°F. Rapid heating, enabled by the use of a small particle size, minimizes secondary condensables' decomposition reactions, thus increasing the yield of valuable condensable hydrocarbons. The literature also showed that lower pressures favor the yield of condensable hydrocarbons. There is some evidence that when steam and CO₂ are used as the mild gasification medium, the deposition and cracking of the condensables on the surface of char particles may be inhibited, thus improving the production

of condensables. Sulfur-capture additives (calcium and iron oxides) may provide catalytically active surfaces for thermally cracking the condensable hydrocarbons and therefore act to decrease tar production. However, these additives have the capability to selectively absorb the H_2S and may even promote the release of sulfur contained in coal.

The analysis of published results for vertical fixed-bed, vertical moving-bed, horizontal moving-bed, fluidized-bed, and entrained-bed low-temperature carbonization processes showed that the higher heat-up rate characteristics of fluidized- and entrained-bed reactors result in the predicted higher yield of condensable hydrocarbons and lower yield of char. The results also suggested that rapid heat-up may produce condensables with a higher pitch content at the cost of lighter oils. The survey also revealed that there was no commercial technology to process caking coals under rapid heat-up conditions to favor the production of condensables. However, there was strong evidence from recent developments in fluidized-bed gasifiers that a suitable reactor configuration could be developed.

The market survey for char identified the production of form coke, smokeless fuel, and adsorbent char as the value-added uses. The char resulting from rapid heat-up of caking coals would improve the quality of the form coke produced by blending with raw coal as the binder. Part of the product fuel gas or char fines, would be burned to produce flue gases for drying and preheating the coal and for mild gasification of feed coal. The excess gas would be available for other fuel uses, such as power generation.

The concept of integrating the conceptual mild gasification process with the mine-mouth coal preparation plant was analyzed to assess the techno-economic benefits of utility fuel production. A case was analyzed in which the coal fines from the preparation plant are fed to the mild gasification reactor, and the resulting char is again blended with the preparation plant coal product. Several benefits could be realized from this integration scheme. These benefits include conservation of energy in drying the -1/2-in.-size fraction by mixing the hot char with the moist coal stream. In addition, it is possible to reduce the amount of fines when some of the coal passes through the plastic range as it comes in contact with 1200°F char. The excess product fuel gas could also be used to dry the remaining 2-in. x 1/2-in. steam coal product to earn a premium on fuel value. Alternatively, the gas could be

used in combined-cycle power generation and char fines combustion employed for coal drying.

Based on the market and literature survey results, a rapid heat-up mild gasification reactor design was selected, so that the maximum yield of value-added condensable hydrocarbons, rich in pitch and aromatics, could be produced.

Following a review of the most recent experience with gasification of caking high-volatile bituminous coals at IGT and elsewhere, a gasifier consisting of fluidized-bed and entrained-bed stages was selected. The two reactor stages had independent coal feed systems. The primary reason for selecting a combination of the two gas-solid contacting schemes was to provide optimum reaction conditions for widely differing coal particle size.

For preliminary engineering evaluation purposes, one-third of the feed coal was to be fed to the entrained bed, and two-thirds was to be fed to the fluidized-bed reactor. A 1000 ton/day mild gasification reactor, heated with 2000°F flue gases, was estimated to require a fluidized-bed stage of 12 ft ID coupled to an entrained-bed stage of 6 ft ID. The char is withdrawn from both the fluidized bed and the entrained bed coupled to a solids-disengaging cyclone. Three of these reactors will be required for a 1 million ton/yr mild gasification plant. Reactor redundancy will provide advantages in operational continuity; thus the size was selected to allow less expensive shop fabrication rather than field fabrication techniques.

An order of magnitude (scoping) capital and operating cost estimate for a million ton/yr conceptual mild gasification plant was prepared using conservatively estimated product costs for the following three char utilization options:

- I. Char blended with coal for utility fuel
- II. Char briquetted with coal fines and then carbonized to metallurgical form coke
- III. Char briquetted with coal fines for use as a smokeless domestic, district-heating, or industrial fuel.

Table ES-1 illustrates the approximate economics in terms of 1988 \$ for the process options above. Options II and III for the two char-derived fuels (metallurgical form coke, smokeless fuel briquettes) show potential for

attractive return on investment in the 25% to 30% range. Option I for char blending with the preparation plant washed coal products shows a much smaller return. However, this assessment reflects a very conservative evaluation of the char fuel value contribution to the total fuel product. The estimated net operating profit does not include debt service charges, taxes, or facility amortization.

Table ES-1. ECONOMIC SUMMARY OF THREE MILD GASIFICATION PROCESS OPTIONS

	<u>Total Capital Requirement</u>	<u>Annual Operating Costs</u>	<u>Annual Plant Revenue</u>	<u>Simple Return on Investment</u>
Option I				
Char to Utility Fuel	143.4	91.8	99.6	5
Option II				
Char to Form Coke	226.4	60.4	117.5	25
Option III				
Char to Smokeless Fuel	169.1	58.5	110.0	30

PROJECT GOALS

The U.S. demand for oil and gas is increasing steadily, and by 1995 the nation could be dependent for nearly two-thirds of its energy requirements on imported oil and gas. Meanwhile, the fraction of energy provided by its largest fossil resource -- namely, coal -- is declining. The U.S. Department of Energy (DOE) notes that the real opportunities for coal to displace oil and gas exist in the industrial, commercial, transportation, and residential sectors. By capturing 25% of the energy need for these sectors, the current coal consumption could be increased by 50%. In addition, a coal conversion technology that is affordable in the present economic climate, and which could be commercialized within the next 5 to 10 years, will significantly benefit the coal industry and the nation. With these general goals in mind, DOE is sponsoring this technology development project to produce value-added, coal-derived co-products by low-cost and simple mild gasification of coal.

The mild gasification of coal is a process that has the potential to produce readily usable condensable hydrocarbons, fuel gas, and char. Mild gasification is a modification of conventional coal gasification processes, employing low-severity or mild operating conditions, producing a suite of co-products suitable for industrial, commercial, residential, and transportation sectors.

The primary objective of this DOE-sponsored project, involving the team effort of a coal company (Peabody Holding Co., Inc.), a process developer (Institute of Gas Technology), and an engineering company (Bechtel National, Inc.) is to develop an advanced mild gasification process to produce coal-derived co-products that can readily open new markets for coal in both the utility and nonutility sectors. The study will incorporate novel and innovative concepts for process development and for co-products utilization. The former includes the development of a means to promote the rapid, continuous devolatilization of caking coals, the use of inexpensive reactor additives for capturing sulfur compounds, and the use of inexpensive reaction gases to produce co-products of optimal quality and quantity. It is the ultimate goal of this project to commercialize the advanced mild gasification technology in the next 5 to 10 years.

APPROACH

The approach to the development of an advanced, mild coal gasification process was based on a detailed literature survey and review of the state-of-the-art of coal conversion to readily saleable co-products. A market survey, conducted concurrently with the literature survey, has identified the priority end uses. Based on this information, the type of reactor and operating conditions and the methods of co-products upgrading to be used as a basis for design were determined. Although it is recognized that the co-products of mild gasification may not be superior to the conventional alternatives, it is very likely that the design and specifications of the present equipment could be modified to utilize the coal-derived products.

The end uses for the co-products are determined by their quality and process economics. It is conceivable that the quality and quantity of the co-products can be optimized by choosing appropriate temperatures, gas-solid contacting mechanisms, reaction gas compositions, and the use of reactor additives. There are several end uses for the condensable hydrocarbons -- as a feedstock for coal tar processing; fuel for transportation, industrial, and strategic applications; and as a chemical feedstock. The fuel gas can be used onsite as an industrial fuel or to fuel power production facilities employing combined-cycle or combustion engines. The char can be used in both utility and nonutility applications, which include combustion of the char mixed with pulverized coal. The char may also be used as a smokeless domestic or district heating fuel, as a substitute for metallurgical coke for a variety of industrial applications, as an adsorbent char, and as a gasification feedstock to produce carbon black, H_2 , or synthesis gas.

The Institute of Gas Technology (IGT) has formed a team with Peabody Holding Co., Inc. and Bechtel National, Inc. (BNI) to develop an advanced, continuous mild gasification process for the production of co-products. IGT and BNI with their extensive process development and design experiences, have conducted the literature surveys. Peabody, closely interacting with IGT and BNI, has ensured that the technology development objectives are consistent with the needs, long-range growth, and expansion goals of the coal industry. Peabody has also evaluated the utility market for the co-product char. Peabody, BNI, and IGT have conducted the market assessment of co-products, reviewed and evaluated the choice of a mild gasification process development

reactor system for testing at half-ton coal per day capacity, and conducted a preliminary economic evaluation of a conceptual commercial process of 1 million tons-per-yr coal capacity.

The results of the above approach are presented on the following pages. First, the literature survey of mild gasification processes is described, leading to an analysis of published results that formed the basis for selecting a range of operating conditions and an advanced reactor concept. Second, the results of the literature survey of co-products upgrading and utilization methods are presented, discussing the appropriate alternatives that could benefit the commercialization of mild gasification technology. Third, the findings of the market assessment for the mild gasification co-products are presented. The market survey results determined the specific details of the advanced mild gasification reactor for processing high-volatile agglomerating bituminous coals. Fourth, the results of a preliminary economic analysis for a commercial plant of a million tons of coal per year capacity, producing a selected slate of co-products, were estimated. In conclusion, the technology development needs for mild gasification and co-products upgrading and utilization, including the commercialization plan, are presented.

TASK 1. LITERATURE SURVEY AND MARKET ASSESSMENT

Subtask 1.1. Literature Survey of Mild Gasification Processes

Objective

The objective of this subtask is to conduct a review of the published literature on low-temperature carbonization, pyrolysis, and devolatilization, with particular emphasis on processing high-volatile bituminous coals. It is also the objective of this subtask to determine 1) the effect of rapid gas-solid contacting methods, reactive gas media, sulfur capture additives, and coal pretreatment on process yields and 2) the fate of heteroatoms during mild gasification.

Introduction

The literature survey covered the period of 1963 to 1987, with emphasis on the period of 1967 to 1987. A computer search of the DOE Energy Database yielded over 3000 titles of journal articles, reports, and conference papers on topics related to mild gasification. Of these titles, about 560 abstracts were reviewed, and a total of 138 papers were obtained for detailed study. An additional 40 recent papers on file at IGT were included in the survey. A detailed study was also made on over 30 reports to DOE or the Electric Power Research Institute (EPRI), 12 books, and several industrial research bulletins on coal devolatilization, product upgrading, product utilization, and related topics.

Extensive literature is available on the fundamental effects of various processing conditions on the devolatilization behavior of coals over a wide range of conditions, based on bench- and laboratory-scale investigations.¹⁻⁵ This literature includes almost all of the current DOE-sponsored research on fundamental devolatilization and mild gasification process development. Comprehensive information from pilot plants and industrial operations is also available.⁶⁻¹⁴ Larger-scale studies have generally been focused on a particular end use for the products, such as substitute fuels or substitute metallurgical coke; in some cases, important process performance data are not divulged for proprietary reasons.

Most of the following data have been gleaned from well-documented laboratory studies, augmented with larger-scale data wherever possible. The effects of coal type, temperature, pressure, particle heating rate, and

particle size are discussed, as well as the effects of sulfur-capture additives, reactive gas media, and coal pretreatment.

Effect of Operating Conditions on Devolatilization Characteristics of Coal

Effect of Coal Type

The U.S. coals range in rank from lignites to anthracite. The most extensive reserves close to major population centers consist of the high-volatile eastern bituminous coals. These coals generally contain relatively high amounts of sulfur, in both the inorganic (pyritic) and organic forms and, thus, are limited in marketability through conventional channels due to environmental considerations. These coals also display extreme caking tendencies.

As shown in Figures I-1 to I-3 the devolatilization yield and distribution of pyrolysis products depend on the rank of coal. In the mild gasification temperature range of 900° to 1500°F (482° to 816°C), the two hvbA coals (PSOC 268 and PSOC 124) showed a higher total devolatilization yield, as well as a higher primary tar yield, than the lower rank lignite and hvbC coals shown in Figure I-1.¹⁵ Figure I-2 shows similar trends for three low-rank coals compared to Pittsburgh seam coal.¹⁶ In Figure I-3, the devolatilization of four German coals ranging from high-volatile to low-volatile bituminous are compared, which shows that the tar yield begins to decline as the coalification proceeds through the bituminous range toward anthracite, as the volatile matter (V.M.) content decreases.¹⁷ Investigators at CSIRO have shown data that relates the yield and composition of condensables from bituminous and subbituminous coals devolatilized in a fluidized bed to the H/C atomic ratio of the coal.¹⁸ Figure I-4 shows how the tar and total devolatilization yields at 1112°F (600°C) varied with the coal H/C atomic ratio in that study. It is evident from all of these studies that the high-volatile bituminous coals produce the highest yields of condensable devolatilization products.

The distribution of gaseous devolatilization products is also dependent on rank, as shown in Figure I-5.¹⁹ The lower-rank coal produces more water and CO_x species and less gaseous hydrocarbons. The higher oxygen content of the lower-rank coals is also reflected in the higher oxygen content of the condensable stream reported by Che et al. and illustrated in Table I-1.²⁰

Figure I-1. YIELD AND DISTRIBUTION OF DEVOLATILIZATION PRODUCTS FOR THREE BITUMINOUS COALS AND ONE LIGNITE¹⁵

Figure I-2. COMPARISON OF DEVOLATILIZATION YIELDS FOR THREE LOW-RANK COALS AND PITTSBURGH SEAM COAL¹⁶

No. on Curves	Coal Rank	VM, (wt % maf)
1	Anthracite	5.9
2	Low Volatile	16.3
3	Med. Volatile	22.7
4	High Volatile	32.4
5	High Volatile	36.4

Figure I-3. TAR YIELDS FOR FIVE HIGH-RANK COALS UNDER NITROGEN
AT VARYING PRESSURES AND HEATING RATES¹⁷

Figure I-4. VARIATION IN DEVOLATILIZATION YIELDS AT 1112°F WITH H/C ATOMIC RATIO OF COAL¹⁸

Figure I-5. EFFECT OF COAL TYPE ON DEVOLATILIZATION PRODUCT GAS YIELDS¹⁹

Table I-1. COMPARISON OF COALS OF DIFFERENT RANKS AND THEIR LIQUID PRODUCTS

<u>Coal</u>	<u>Wyoming Subbituminous</u>	<u>Kentucky No. 9 Bituminous</u>
H/C, Atomic Ratio	0.82	0.89
Oxygen, %	20.1	7.5
Sulfur, %	0.65	3.5
Nitrogen, %	1.2	1.7
Fischer Tars, %	9.7	16.3
<u>Liquid Product*</u>		
Yield, %	21.0	33.0
H/C, Atomic Ratio	1.1	1.05
Oxygen, %	14.1	7.9
Sulfur, %	0.45	2.1
Nitrogen, %	1.0	1.4

* From Occidental Flash Pyrolysis.²⁰

The heteroatom content of the products is, of course, determined primarily by the heteroatomic content of the parent coal. Physical cleaning of coal prior to mild gasification can significantly reduce sulfur by removing a portion of the pyrite. Other factors that influence the S, N, and O levels in the products include temperature, particle heating rate, and the presence or absence of sulfur capture additives in the gasification step. These factors will be discussed in subsequent sections.

The effect of coal type is not limited to the yields and distribution of products; the caking properties of the coal, which are related to coal rank, play a major role in the selection of process configuration and reactor design. This topic will be discussed in detail in later sections of this report.

Effect of Temperature

As shown earlier in Figures I-1 and I-2, the total devolatilization yield for bituminous coals increases rapidly in the range of 750° to 1300°F (400° to 700°C), then increases more slowly, as char gasification becomes more

significant.^{15,16} It has been shown that the overall devolatilization yield for any coal is independent of heating rate at a given final temperature,¹ although secondary reactions of the volatile products can generate tar carbonization solids that are indistinguishable from primary char. Studies at CSIRO to determine the effect of fluidized-bed reactor designs and coal type on devolatilization yields showed that the yield of condensable hydrocarbons, regardless of the coal studied, reached a maximum at about 1112°F (600°C).¹⁸ Data from other investigators, as shown in Figures I-1 and I-2, gave similar results.³ The maximum condensable product yield from devolatilization in inert gas is between 20% and 30% by weight of the moisture and ash-free (maf) coal. As temperature increases, secondary reactions will reduce the amount of recoverable condensables, which is reflected in the fact that the tar yield from conventional high-temperature carbonization (coking) is generally about 8%.

The extent of secondary reactions is to a large degree dependent on the reactor configuration. The data of Kobayashi,²¹ illustrated in Figure I-6, shows the complex relationship between final temperature and heating rate on the pattern of elemental change during devolatilization; Figure I-7 shows data from the same study for a lignite and a bituminous coal, using only the fixed-bed (crucible) cases. Between 900°F and 1500°F, there are substantial changes in the patterns of evolution of gaseous species containing S, N, and O atoms. The release of oxygen and hydrogen from char approach completion at a lower temperature than the release of nitrogen and sulfur.

In a study at United Technologies,²² nitrogen distributions from the vacuum pyrolysis of 13 coals were reported. Figure I-8 shows that the concentration of nitrogen compounds in the gas phase increased sharply over the region of 1076° to 1580°F (580° to 860°C). The nitrogen content of tar, on the other hand, remained quite constant over these temperatures, and the nitrogen content of the char increased gradually.

The conversion of coal sulfur to H₂S, the principal gaseous sulfur-containing devolatilization product, is shown in Figure I-9 for three bituminous coals;²³ it is evident from these data that the pattern of sulfur conversion to gas will vary considerably from one coal to another, possibly dependent on the distribution of sulfur among organic and inorganic forms in the coal. In the mild gasification temperature range, however, the sulfur

Figure I-6. ELEMENTAL COMPOSITION OF COAL CHARS CARBONIZED AT DIFFERENT TEMPERATURES AND PARTICLE RESIDENCE TIMES²¹

Figure I-7. ELEMENTAL COMPOSITIONS OF COAL CHARs DEVOLATILIZED IN A CRUCIBLE AT TEMPERATURES FROM 400° TO 2000°C²¹

Figure I-8. NITROGEN CONCENTRATION IN DEVOLATILIZATION PRODUCTS
AT VARIOUS TEMPERATURES²²

PITTSBURGH SEAM (●),
ILLINOIS NO. 6 (■), AND MO-KAN (▼)
COALS

Figure I-9. CONVERSION OF COAL SULFUR TO H₂S FOR THE
DEVOLATILIZATION OF THREE BITUMINOUS COALS²³

conversion to H_2S has been observed to increase slowly, as illustrated in Figure I-10.²⁴ The sulfur content of tar is generally somewhat lower than the sulfur content of the parent coal, as shown by the examples in Table I-2, where tars and chars from Occidental Flash Pyrolysis,⁶ COED,¹⁴ and ORNL²⁵ tests were compared with feed coals for total sulfur content. There is also a noticeable variation in the char sulfur levels relative to the feed coal, with two of the chars having higher sulfur levels than the coal, and one lower.

Table I-2. COMPARISON OF SULFUR CONTENT IN TARS FOR THREE LOW-TEMPERATURE CARBONIZATION PROCESSES

Process Name	Occidental	COED	ORNL
Test No.	175	P-45	--
Temperature, °F	1220	1100	932
Reactor Type	Entrained Bed	Fluidized Bed	Fixed Bed
Parent Coal	W. Kentucky #9	Illinois #6	W. Kentucky #9
Sulfur in Coal, wt % (dry)	3.0	4.0	5.8
Sulfur in Tar, wt % (dry)	1.7	2.0	1.9
Sulfur in Char, wt % (dry)	3.3 (by diff)	5.6 (stage 3)	3.66

Oxygen is evolved from coal by two mechanisms: generation of devolatilization water, which begins around 700°F (371°C), and generation of carbon oxides, which begins at about the same temperature and increases gradually, peaking at about 1500°F (816°C). Figure I-11 shows how the evolution of oxygen-bearing gases changes with temperature for a bituminous coal.²⁶ The oxygen content of tar is related to the degree of secondary decomposition that takes place as well as the final temperature. Table I-3 compares the oxygen content of tars produced in Occidental Flash Pyrolysis tests using char and petroleum coke as heat carriers.⁶ The char heat carrier was observed to enhance secondary reactions relative to the petroleum coke.

For a given reactor system, the following statements summarize the effects of increasing devolatilization temperature:

- Condensable hydrocarbons will undergo thermal cracking reactions to yield light gases, light oils, and secondary char^{1,3}

Figure I-10. DEVOLATILIZATION PRODUCT DISTRIBUTION, INCLUDING H₂S, FOR COAL HEATED TO VARIOUS TEMPERATURES²⁴

Figure I-11. EVOLUTION OF GASES FROM DEVOLATILIZATION OF BITUMINOUS COAL AS A FUNCTION OF TEMPERATURE²⁶

Table I-3. COMPARISON OF OCCIDENTAL FLASH PYROLYSIS TARS FROM
BITUMINOUS COAL WITH TWO DIFFERENT HEAT CARRIERS⁶

Test No.	154	171
Heat Carrier	Subbituminous char	Petroleum coke
Transport Gas	CO ₂	CO ₂
Temperature, °F	1035	1120
Residence Time, s	1.5	1.5
<u>Tar Composition, wt %</u>		
C	83.2	79.2
H	7.8	6.9
S	2.1	1.7
N	1.2	1.8
O (by diff)	5.7	10.4
H/C atomic ratio	1.10	1.05
<u>Solubility Classification, wt % of tar</u>		
Oils	77	60
Asphaltenes	4	24
Preasphaltenes	19	16

- The condensables will increase in aromaticity as aliphatic side chains are removed from the structures by thermal dealkylation (Table I-4)¹²
- The condensables and char will tend to lose sulfur and oxygen, but nitrogen content will generally remain unchanged up to about 1300°F, when the nitrogen content of char begins to decline (Figures I-6, I-7, and I-12)²⁷
- The pitch content of the condensables and the overall yield of pitch increase (Table I-5)²⁶⁻²⁸
- The BTX (benzene, toluene, xylenes) yield and the relative fraction of benzene in BTX increase (Table I-5)^{5,13,28}
- The PCX (phenol, cresols, xylenols) yield decreases and the relative fraction of phenol in PCX increases (Table I-5)^{5,13,28}
- The char V.M. decreases as shown in a plot of data from Protopapas et al., (Figure I-13).¹²

Table I-4. COMPARISON OF LIGHT OIL COMPONENTS FROM LOW-, MEDIUM-, AND HIGH-TEMPERATURE CARBONIZATION¹²

<u>Composition of Condensable Compounds From Coal Gas, wt %</u>			
	<u>Coke Oven (1850°F)</u>	<u>Continuous Vertical Retort (1500°F)</u>	<u>Low-Temperature Retort (1200°F)</u>
Monoolefins	1.64	2.33	16.26
Dienes	2.48	2.58	1.36
Cycloolefins	5.37	1.16	9.55
Paraffins	0.34	22.37	46.53
Naphthenes	0.21	3.62	8.00
Aromatics	85.26	63.04	15.56
Indene	1.13	0.72	0.15
Carbon Disulfide	0.40	0.66	0.06
Thiophenes	0.67	0.33	0.66
Other Compounds	2.50	3.19	1.87

Effect of Pressure

The effects of pressure on devolatilization products and their compositions are interdependent with the effects of the gas medium in which devolatilization takes place. For coal devolatilization in an inert gas medium, it has been reported in several independent investigations that the

Figure I-12. COMPARISON OF COAL NITROGEN IN TAR WITH TAR YIELD²⁷

Table I-5. COMPARISON OF CONDENSABLE DEVOLATILIZATION PRODUCT COMPOSITIONS FROM COKE OVENS (~1800°F), CVR RETORTS (~1500°F), AND LOW-TEMPERATURE RETORTS (~1200°F)²⁸

Component, wt % of dry tar	Coke-oven tars					CVR tars, UK			Low temperature tars, UK av
	UK		FRG av	US av	Range		UK av		
	Av	Range			Av	Range			
benzene	0.25	0.12-0.42	0.4	0.12	0.22	0.14-0.26	0.01		
toluene	0.22	0.09-0.35	0.3	0.25	0.22	0.17-0.29	0.12		
<i>o</i> -xylene	0.04	0.02-0.07		0.04	0.06	0.05-0.08	0.05		
<i>m</i> -xylene	0.11	0.08-0.18	0.2	0.07	0.13	0.11-0.18	0.10		
<i>p</i> -xylene	0.04	0.02-0.07		0.03	0.05	0.04-0.07	0.04		
ethylbenzene	0.02	0.01-0.05		0.02	0.03	0.02-0.04	0.02		
styrene	0.04	0.02-0.04		0.02	0.04	0.02-0.06	0.01		
phenol	0.57	0.14-1.15	0.5	0.61	0.99	0.49-1.36	1.44		
<i>o</i> -cresol	0.32	0.10-0.34	0.2	0.25	1.33	0.77-1.53	1.48		
<i>m</i> -cresol	0.45	0.16-1.0	0.4	0.45	1.01	0.58-1.33	0.98		
<i>p</i> -cresol	0.27	0.07-0.70	0.2	0.27	0.86	0.50-1.03	0.87		
xlenols	0.48	0.13-1.30		0.36	3.08	2.70-3.58	6.36		
high boiling tar acids	0.91	0.31-2.09		0.83	8.09	6.57-11.1	12.89		
naphtha	1.18	0.52-2.66		0.97	3.21	2.86-3.84	3.63		
naphthalene	8.94	7.29-11.31	10.0	8.80	3.18	2.15-3.84	0.65		
α -methylnaphthalene	0.72	0.60-0.86	0.5	0.65	0.54	0.46-0.64	0.23		
β -methylnaphthalene	1.32	1.15-1.63	1.5	1.23	0.68	0.62-0.74	0.19		
acenaphthene	0.96	0.42-1.28	0.3	1.05	0.66	0.50-0.80	0.19		
fluorene	0.88	0.46-1.80	2.0	0.64	0.51	0.33-1.23	0.13		
diphenylene oxide	1.50	1.40-2.00	1.4		0.68	0.62-0.74	0.19		
anthracene	1.00	0.52-1.38	1.8	0.75	0.26	0.18-0.30	0.06		
phenanthrene	6.30	2.30-9.80	5.7	2.66	1.75	0.40-2.90	1.60		
carbazole	1.33	0.58-1.73	1.5	0.60	0.89	0.14-1.43	1.29		
tar bases	1.77	1.25-2.60	0.73	2.08	2.09	1.81-2.17	2.09		
medium soft pitch	59.8	49.5-63.9	54.4	63.5	43.7	41.0-49.3	26.0		

CHAR VOLATILE MATTER

from 15 coal carbonization processes

Figure I-13. CHAR VOLATILE MATTER RELATIVE TO COAL VOLATILE MATTER AS A FUNCTION OF TEMPERATURE FOR THREE TYPES OF CARBONIZATION PROCESSES

total devolatilization yield decreases with increasing pressure.¹ At elevated pressures secondary decomposition reactions are favored by the inhibition of the escape of volatile material from the coal particle, as well as by increasing the probability of molecular collisions between the reactive condensable fragments. Figures I-3, I-14,²⁹ and I-15²⁹ show this effect, which becomes significant when the temperature exceeds about 1300°F (700°C).^{1,3}

In the presence of reactive gases, however, the situation is quite different. Hydrogen has been used to enhance the conversion of volatile matter from devolatilization of coal, as well as increasing the H/C ratio of the condensable products, primarily to enhance the attractiveness of these products for further processing to substitute liquid fuels. The effect of hydrogen on the devolatilization of coal is related to the hydrogen partial pressure as shown in Figure I-16.¹

Devolatilization experiments in the presence of other reactive gases, such as steam, have shown that the yield of condensables does not decline in the presence of these media as with inert gases -- and may actually be enhanced at higher pressures. A recent paper reports that the condensable yields can be improved even at low pressures under CO and H₂ in the presence of shift catalysts, presumably by the generation of nascent hydrogen.³⁰

It does not appear, however, that the effect of pressure on product yields would be significant over the relatively small range (0 to 50 psig) considered for mild gasification. The concept of mild gasification dictates simple and economic design and operating conditions, achievable by low-pressure or ambient-pressure processes. Operation at pressures above atmospheric, however, may increase throughput.

Effect of Reactive Gas Composition

Several investigators^{4,9,31} have reported increased yields of condensable products from devolatilization experiments in the presence of reactive gases such as H₂, CO₂ and steam, in comparison to inert gases. As mentioned previously, this effect may be partly attributable to the reactions of condensable fragments with the ambient gas, in the cases of hydrogen and steam. An additional effect has been suggested.³¹ The active char surface generated by devolatilization provides convenient sites for tar cracking reactions, as

Figure I-14. EFFECT OF HELIUM PRESSURE ON TAR YIELD FROM PITTSBURGH SEAM COAL AT VARIOUS DEVOLATILIZATION TEMPERATURES²⁹

Figure I-15. EFFECT OF SUBATMOSPHERIC HELIUM PRESSURE ON PRODUCT YIELDS FROM DEVOLATILIZATION OF PITTSBURGH SEAM COAL²⁹

Figure I-16. EFFECT OF HYDROGEN PRESSURE ON COAL CONVERSION¹

shown by the data in Table I-6;⁶ reactive gases may tend to compete for these sites, inhibiting the secondary decomposition reactions of the condensables.

Table I-6. PROPERTIES OF FLASH PYROLYSIS TARS PRODUCED AT DIFFERENT OPERATING CONDITIONS

Run	Heat Carrier	Gas Medium	Temp, °F	Residence Time, s	Tar Yield, wt % maf	H/C Ratio	O, wt % maf
180	Pet. Coke	CO ₂ /steam	1190	1.3	31.9	0.94	8.2
173	Pet. Coke	CO ₂ /steam	1200	2.1	27.2	0.97	8.8
172	Pet. Coke	CO ₂ /steam	1200	4.2	24.0	1.02	9.5
174	Pet. Coke	N ₂	1220	3.8	24.3	0.97	8.6
175	Pet. Coke	N ₂	1220	1.4	25.0	1.08	10.6
176	Pet. Coke	CO ₂	1130	4.1	27.9	1.07	12.0
177	Pet. Coke	CO ₂	1130	1.5	34.6	1.06	9.6
178/179	Pet. Coke	CO ₂	1220	1.3	34.5	1.03	8.7
170	Pet. Coke	CO ₂	1190	4.2	20.5	1.01	8.5
154	Subbituminous Char	CO ₂	1035	1.5	5.0	1.10	5.7
155	Subbituminous Char	CO ₂	1013	4.4	9.0	1.11	5.9

In the presence of hydrogen at significantly high partial pressures, the aromaticity of the condensable products has been observed to increase, due to the removal of aliphatic side chains from the aromatic tar structures accompanied by the generation of hydrocarbon gases.³²

In addition to these effects, studies at Brookhaven National Laboratories³³ have also shown that devolatilization in the presence of CH₄ may also enhance yields of BTX and ethylene, which are considered to be valuable chemical by-products; it is uncertain whether increased yields of ethylene are primarily derived from the coal structure or from thermal disproportionation of methane.³⁴

With regard to the effects of various gas media on other properties of coal, a study using low-pressure He, H₂, N₂, Ar, and CO₂ with Lower Kittanning Seam bituminous coal has shown no effect of ambient gas variation on thermoplastic behavior.³⁵

The fact that the fuel gas generated by coal devolatilization contains reactive gases (that is, CO_2 , H_2 , CO , H_2O , light hydrocarbons) suggests that recycling a portion of the fuel gas to the mild gasification reactor may enhance the yield and value of condensable products. It is also conceivable that a steam- or CO_2 -rich flue gas stream could constitute a reactive gas medium, with the associated potential for improvements in the yield of condensable products.

Effect of Particle Heating Rate

The heating rate of the coal particle influences the degree of secondary decomposition of devolatilization products. The particle heating rate and particle size are interrelated, and these parameters are intimately related to the mild gasification reactor configuration. Most of the reported studies in the literature describe work with fine particles where the rate of heating has been closely controlled.¹

If the possible reactor types are grouped into broad categories, particle heating rates in these reactors conform to the following trend:

[fixed bed < moving bed < fluidized bed < entrained bed]

The particle heating rates range from about $2^\circ\text{F}/\text{min}$ in fixed beds to $10^6^\circ\text{F}/\text{min}$ in entrained-bed reactors.

Several comparisons have been made between the results of devolatilizing the same coal under slow-heating and rapid-heating conditions.^{1,5,36} In a comparison of condensables obtained from a Utah high-volatile bituminous coal using Lurgi-Ruhrgas (rapid heating) and Wellman-Galusha (slow heating) techniques,^{36,37} it was reported that the tar produced by rapid heating contained more heteroatoms, less hydrogen, and a higher average molecular weight. Table I-7 shows some of the properties of these two tars. The differences between the Lurgi-Ruhrgas and Wellman-Galusha tars result in part from the countercurrent steam and gas stripping of the feed coal in the moving bed of the latter versus the cocurrent contacting in the former process. Tables I-8 and I-9 compare the product distribution and tar compositions resulting from slow- and rapid-heating devolatilization of German bituminous coals under otherwise similar conditions.⁵ It is apparent from these two tables that higher pitch yields can be produced by rapid heating of coal. Figure I-3 also showed how particle heating rate affects the overall yield of condensables from higher-rank coals.¹⁷

Table I-7. PROPERTIES OF CONDENSABLES FROM RAPID AND SLOW HEATING RATE DEVOLATILIZATION OF UTAH hvb COAL³⁷

Process	Total Tar Yield, * %	Tar Yields and Conventional Analyses					
		Elemental Composition, %					
		C	H	N	O†	S	C/H
Lurgi	21**	82.70	6.02	1.20	9.63	0.40	13.7
Wellman-Galusha	14.8	83.98	9.13	0.86	5.83	0.30	9.2

* Weight % moisture free coal.

** Yield not corrected for insoluble tar compounds (estimated at 5%-10% of total tar).

† By difference.

Table I-8. PRODUCT DISTRIBUTION FROM RAPID AND SLOW HEATING RATE DEVOLATILIZATION OF GERMAN BITUMINOUS COAL⁵

Product	Yield, g/kg		Ratio of Rapid-to-Slow
	Rapid	Slow	
Gas	70.0	100.0	0.70
Coke-Water	75.0	81.0	0.93
Light Oil	18.7	41.2	0.45
Middle Plus Heavy Oil	82.3	54.1	1.52
Pitch	86.0	16.7	5.15
Low-Temperature Coke	668.0	707.0	0.94

In general, slow heating of particles, such as the case in the Fischer Assay procedure, favors secondary reactions of volatiles, which produces the following effects:

- Lower overall condensables yield
- Higher overall char and gas yield
- Higher yield of light oils
- Lower yield and concentration of pitch.

Table I-9. COMPOSITION OF CONDENSABLE PRODUCTS FROM RAPID AND SLOW HEATING RATE DEVOLATILIZATION OF GERMAN BITUMINOUS COAL⁵

	<u>Rapid</u> <u>Carbonized Tar</u> ----- wt % oil tar -----	<u>Fischer Tar</u> -----
Aliphatics Determined by Urea Method	4.254	6.366
Paraffins	2.30	7.14
Olefins	<u>2.86</u>	<u>3.35</u>
Total Aliphatics	5.16	10.49
1-Ring Aromatics	1.52	5.27
2-Ring Aromatics	3.86	5.73
3-Ring Aromatics	6.22	6.55
4-Ring Aromatics	2.85	9.27
5-Ring Aromatics	0.48	0.40
Phenols	14.10	25.92
Bases	0.28	2.46
Pitch Residue	64.6	27.7

Because of the extensive decomposition of primary heavy tars to gases, light oils, and char during devolatilization, the net liquid product from slow heating will contain a larger proportion of PCX, BTX, tar bases, and naphthenic components than the product from devolatilization under rapid-heating conditions at the same temperature and pressure.⁵

In contrast to slow heating, rapid heating of particles produces the following effects:

- Higher overall condensables yields
- Higher yield and concentration of pitch (distillation residue) in the tar
- Higher aromatic content of condensables
- Higher content of heteroatoms in high-boiling tar fractions.

Under rapid-heating conditions, the devolatilization products vaporize quickly and diffuse out of the particle in a shorter time, becoming diluted by the bulk gas stream. Once diluted by ambient gases, the frequency of molecular collisions between the reactive fragments is reduced, and secondary decomposi-

tion reactions are less likely. The presence of a reducing gas medium will tend to stabilize the condensable products.

In addition to the effects on the volatile products, the heating rate also affects the physical structure of the char. Rapid heating, by producing volatile products faster than they can escape through the existing pore structure, causes deformation of the particle in its incipient plastic state. This results in an expanded spherical particle with an enlarged pore structure and greatly increased surface area. In contrast, slow heating produces a char not much different in physical appearance and density from the parent coal. This is illustrated in Figure I-17.⁵

Effect of Particle Size

As previously stated, the effect of particle size on devolatilization can be viewed as the inverse of the effect of heating rate. As particulate size increases, the residence time of the volatiles released within the pores of the particle also increases, thus subjecting these substances to a series of secondary decomposition reactions.

Effect of Sulfur-Capture Additives

Particulate mineral additives can be used in a devolatilization reactor to capture the H_2S produced from the sulfur in coal. Khan³⁸ has shown that the concentration of H_2S in the product gases can be reduced by two or more orders of magnitude by devolatilizing coal mixed with lime; the sulfur content of tars may also be reduced by this method, although to a much lesser degree. For this form of in-situ desulfurization to be effective, intimate mixing of the reactive solid and gaseous phases, such as in a fluidized bed, would be beneficial.

Additives that can be effective in reducing sulfur in this way include lime (CaO) and iron oxide (Fe_2O_3). The sulfided products, which are retained in the char, are CaS and FeS , respectively. Lime offers the added advantage that it could be left in the char product, since subsequent carbon conversion under oxidizing conditions can convert the CaS to $CaSO_4$, which can be safely disposed of with the char ash. The necessity for char separation from the additive would exist when iron oxide is used as an additive.

It should be noted that in addition to the effect of the additive on the sulfur content of the volatile products, lime has been shown to promote tar

Pore expansion in fat coal in relation to heating rate in granular coking. Heating rates: (a) 0.5°C/min; (b) 3.0°C/min; (c) 260°C/min. Magnification: 3.5-fold; 3-5 mm grains.

Figure I-17. PHOTOMICROGRAPH OF COAL CHARS PRODUCED BY CARBONIZATION AT VARIOUS HEATING RATES⁵

cracking reactions by providing an active surface. The benefits of sulfur removal must be balanced against this side effect when considering the use of a solid sorbent. The additive can also act as a diluent to counteract the caking tendency of bituminous coals, which is an added benefit.

Effect of Coal Pretreatment

Until now caking coals have generally required some form of pretreatment to reduce the agglomerating properties, depending on the reactor configuration and the presence or absence of an inert diluent in the bed. The commonly used pretreatment method is partial oxidation. It has been reported that partial oxidation tends to reduce devolatilization yields.²

Another form of coal pretreatment, which is not inspired by the need to reduce the caking tendency, is steam pretreatment. Graff and Brandes³⁹ found that the yield of condensables from devolatilization of bituminous coal can be increased to about 50% of maf coal by steam treatment at 590° to 660°F, as shown in Figure I-18. The continuing studies may develop an acceptable explanation of this effect that may lead to incorporating a steam pretreatment step in the conceptual process schemes, if similar benefits could be derived at lower operating pressures in the 0 to 50-psig range.

Summary of the Effects of Operating Conditions

In summarizing the findings of the literature survey with respect to the effects of operating conditions on product yields and quality, the following statements can be made:

- Liquid yields are maximized with high-volatile bituminous coals, and lower-rank coals yield gases and tars with higher oxygen content than bituminous coals.
- The degree of primary devolatilization (gases+liquids) increases with increasing temperature, but the distribution of gases and liquids depend on secondary reactions of devolatilization products.
- For a given reactor system, higher temperatures result in: tars cracking to gases and secondary char; the loss of aliphatic side-chains from condensables; a lower heteroatom content in the condensables; a higher pitch content in the condensable product; higher BTX yields; and lower PCX yields.
- Char volatile matter and sulfur content decrease with increasing temperature.
- Carbon oxides in the fuel gas product increase with temperature.

Comparison of Steam Pyrolysis Yields from As-received (open points) and Treated (closed points) Illinois No. 6 Coal at 735 psig.

Figure I-18. DEVOLATILIZATION YIELDS FROM STEAM-TREATED AND UNTREATED BITUMINOUS COAL³⁹

- In inert atmosphere, condensable product yields tend to decrease with increasing pressure, but in reactive atmosphere (H_2O , H_2 , CO_2), condensable yields tend to increase with increasing pressure.
- Reactive gases may inhibit secondary reactions of volatiles, which results in increased condensable yields.
- Particle heating rates by reactor type generally follow the trend:
[fixed bed < moving bed < fluidized bed < entrained bed]
- Slow heating favors secondary reactions of volatiles within coal particles, which results in lower overall condensable yields, more aliphatic components, a lower pitch content in the condensable product, and a composition tending to be richer in thermodynamically stable products. Fast heating favors more rapid release of tars into the gas stream, which results in higher overall condensable yields, a more highly aromatic condensable product, a higher pitch content in the tar, and a product character that tends to be determined by devolatilization kinetics.
- Larger coal particles tend to favor secondary reactions within particles, producing the same results as slow heating rates.
- Sulfur-capture additives such as CaO and Fe_2O_3 can reduce the H_2S content of product gases by several orders of magnitude, but provide catalytic surfaces that tend to promote cracking reactions of condensables. Sulfur-capture additives also reduce the sulfur and oxygen content of condensables, but to a much lesser degree than in the case of the gas phase.
- Oxidative pretreatment reduces caking, but also reduces the volatile products yield and consumes carbon from the coal feed; steam pretreatment below devolatilization temperatures may enhance condensable yields.

Review of Carbonization Processes That Meet the Criteria of Mild Gasification

Many commercial, demonstration, pilot, and bench-scale carbonization processes have been previously reviewed.^{7,10} These are classified as fixed-bed, moving-bed, fluidized-bed, and entrained-bed processes; an overview of these processes is shown in Table I-10.

Fixed-Bed Processes

Batch conversion methods are also known as fixed-bed retorting. The reactor designs have been largely derived from coke ovens modified for low-temperature operation. Some mechanical method is required to remove the solid product, which in some cases is an agglomerated mass, from the reactor vessel. The slow heating and long residence times of several hours promote extensive cracking of tars.

Table I-10. REACTOR CONFIGURATIONS, OPERATING CONDITIONS, AND PRODUCT YIELDS FROM LOW-PRESSURE CARBONIZATION PROCESSES

Process name	Bed Configuration	Coal Type	Temperature, °F	Pressure, psig	Res. Time, hr	Product Yields		
						Char, wt%	Tar/oil, wt%	Gas, scf/t
Coalite	Vertical fixed	Bit	1200	Ambient	4.5	75	9.6	4000
Phurnacite	Vertical fixed	Bit (est)	950-1250	Ambient	4.0	82	2.0	NA
Krupp-Lurgi	Vertical fixed	hvb	1100	Ambient	6.0	85	7.0	2800
Cellan-Jones	Vertical fixed	hvb	1200	Ambient	30.6	75	8.0	5750
Curran-Knowles	Vertical fixed	E. gas coal	1000-1500	Ambient	NA	82.5	20.0	8200
Rexco	Vertical fixed	NC	1300	Ambient	15	68	8.4	21,430
Coalene	Vertical fixed	Bit, subbit	1200	4	1.5-3.0	72.5	16.0	13.5 wt%
UCC	Vertical fixed	No. 8 hvb	1200	Ambient	8.0	74	13	10 wt%
Brennstoff- Technik	Vertical fixed	WC hvb	1200	Ambient	2.0-4.0	75	9.6	4550
Lurgi-Spurgas	Vertical moving	Brown	1100	Ambient	5.0	50.1	9.9	NA
Koppers	Vertical moving	WC hvb	1200	Ambient	21.0	64	10	10,330
Didier-Werke	Vertical moving	WC hvb	1112	Ambient	NA	70	10	3210
Rochdale	Vertical moving	WC	1300	Ambient	NA	77	8.3	867
Koal Krudes	Vertical moving	hvb	1200	Ambient	NA	57.5	8.5	NA
Nat'l Fuels	Vertical moving	Coking hvbD	930	Ambient	NA	63.5	14	8300
Heliopore	Vertical moving	SubbB	1330	Ambient	NA	52.3	4.4	6500
Stansfield	Vertical moving	SubbC	1000	Ambient	NA	56	NA	NA
Lurgi-Ruhrgas	Horiz moving	Lig/subb/hvbB	800-1100	Ambient	1-16 sec	63.4	10.4	2050
Disco	Horiz moving	Pitts hvbA	850	Ambient	NA	75	7.4	3700
Mimura	Horiz moving	WC hvbB	932	Ambient	NA	65.6	3.4	8850
Wanishi	Horiz moving	NC hvb	1022	Ambient	NA	74.9	6.3	NA
Hayes	Horiz moving	Pitts hvbA	1200	Ambient	0.33	69.9	17.7	4490
Shimomura	Horiz moving	C hvbA	930	Ambient	NA	71.5	10.1	5230
Toscoal	Horiz moving	Ill hvbC	900	Ambient	0.08-0.17	73.9	9.2	253
Storrs	Conveyor	Utah bitum	850	Ambient	0.033	70	10	1200
LFC	Rotary tray	subbit	930-1040	Ambient	0.13-0.25	75	18	5 wt%
Hayashi	Fluidized	NC	1500	Ambient	NA	50	8.7	21,670
COED	Fluidized	Ky hvbB	450-1285	6	0.17-1.58	63.5	18.3	7.8 wt%
Consol	Fluidized/stirred	hvb	925	25	0.75-2.0	70	14-25	NA
Singh	Fluidized	hvbC	1300	Ambient	NA	65	7	8200
Cerchar	Fluidized	NC/C hvb	970-1100	Ambient	0.17	71.6	NA	1446
UE&C	Fluidized	Ohio hvb	900	Ambient	NA	71.9	10.5	2640
SRI	Fluidized	C Ala hvb	950	Ambient	0.33	80	10	14,000
USEM	Fluidized/stirred	Ky hvbB	905	Ambient	0.17-0.35	48.7	12.6	NA
CSIRO	Fluidized	WC hvb	930-1100	Ambient	NA	NA	NA	NA
Occidental	Entrained upflow	Wyodak subb	900-1100	50	2 sec	52.0	23.6	17.4 wt%
Occidental	Entrained upflow	Ky hvbC	900-1100	50	2 sec	53.7	32.6	12.3 wt%
Parry	Entrained upflow	Lignite	900	Ambient	0.17	49.7	6.4	5186

NC = non-caking; WC = weakly caking; C = caking
NA = data not available

Currently the only active commercial fixed-bed processes are the Coalite and Rexco processes in the United Kingdom, which has been producing a solid domestic fuel and by-product chemicals for over 40 years. Besides Coalite, processes that have operated on a commercial scale include Phurnacite (Figure I-19), Cellan-Jones (Figure I-20), and Rexco (Figure I-21) in the United Kingdom; Krupp-Lurgi (Figure I-22) in Germany; and Curran-Knowles (Figure I-23) in the United States. The Coalene process (USA) employed superheated steam as heat carrier in a pre-World War II demonstration plant (Figure I-24). The United Coal Company (UCC) is presently operating a 1500-lb-coal/day process development unit that uses a design similar to Coalite to produce coal-derived liquids (Figure I-25); the process was originally designed to produce a char/oil slurry for use in heat engines.

Other fixed-bed processes that have operated on the pilot scale included Brenstoff-Technik (Figure I-26), Otto and Weber (Figure I-27) in Germany, and Carmaux (Figure I-28) in France; all of these were in operation during World War II and were subsequently abandoned. Noncaking coals or briquettes were used as feed, and products included domestic fuel, form coke, tar for chemicals, and char for gas generators.

Moving-Bed Processes

Many designs of continuous moving-bed carbonizers have been used, including vertical and horizontal moving beds, and conveyor-, moving-grate, and rotary-tray designs.

Lurgi-Spülgas (Figure I-29), Koppers (Figure I-30), Geissen (Figure I-31), and Didier-Werke (Figure I-32) in Germany; Rochdale in the United Kingdom; and Koal Krudes (Figure I-33) in the United States have all operated commercially using the vertical moving-bed design. These designs generally used a combination of external and internal heating using hot product gases and flue gases. A demonstration plant was built by National Fuels Corporation and American Cyanamid (Figure I-34) to produce a coke blending stock, also using a vertical moving bed design. Pilot plants have been built in the United States [Heliopore (Figure I-35), Petit (Figure I-36), and Pipestem], Germany [Pintsch-Weber (Figure I-37)], Canada [Stansfield (Figure I-38)], and India (Hyderabad). All of these vertical moving-bed designs have required a feed of either briquettes or double-screened coal without strong caking properties.

Figure I-19. CROSS-SECTION VIEW OF PHURNACITE RETORT

Section thru centre of Cellan-Jones oven at the works of L. & L. Charlesworth Limited

Figure I-20. CROSS-SECTION VIEW OF CELLAN-JONES RETORT

Figure I-21. REXCO LOW-TEMPERATURE CARBONIZATION PROCESS SCHEMES

Figure I-22. CROSS-SECTION VIEWS OF KRUPP-LURGI RETORT

Figure I-23. CROSS-SECTION VIEW OF CURRAN-KNOWLES RETORT

Figure I-24. CROSS-SECTION VIEW OF COALENE RETORT

Figure I-25. LAYOUT OF UCC RETORT SYSTEM

Figure I-26. CROSS-SECTION VIEW OF BRENNSTOFF-TECHNIK RETORT

Figure I-27. LAYOUT OF OTTO AND WEBER LOW-TEMPERATURE CARBONIZATION PLANT

Figure I-28. CROSS-SECTION VIEW OF CARMAUX RETORT

Figure I-29. SCHEMATIC DIAGRAM OF LURGI-SPÜLGAS LOW-TEMPERATURE CARBONIZATION PLANT

Figure I-30. CROSS-SECTION VIEW OF KOPPERS MOVING-BED LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-31. CROSS-SECTION VIEW OF BORSIG-GEISSEN MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

a. Coal bunker	d. Carbonization chamber	g. Coke extractor
b. Cell valve	e. Baffle wells	h. Coke-cooling chamber
c. Predrier	f. Collecting main	i. Coke-discharge valve

Figure I-32. CROSS-SECTION VIEW OF DIDIER-WERKE MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-33. SCHEMATIC DIAGRAM OF KOAL KRUDS LOW-TEMPERATURE CARBONIZATION PLANT

1. Retort	10. Quench or cooling gas
2. Gas-tight feeder	11. Surplus gas
3. Foul gas	12. Tuyeres
4. Primary cooler	13. Heated gases,
5. Cottrell precipitator	oxygen-free
6. Exhaustor	14. Water-sealed discharge
7. Clean gas	15. Carbonized product
8. Air	16. Insulation
9. Combustion mixture	

Figure I-34. SCHEMATIC DIAGRAM OF NATIONAL FUELS MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-36. CROSS-SECTION VIEW OF PETIT MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-37. CROSS-SECTION VIEW OF PINTSCH-WEBER MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-38. CROSS-SECTION VIEW OF STANSFIELD MOVING-BED LOW-TEMPERATURE CARBONIZATION REACTOR

Based on the 25 tons/day (TPD) low-temperature carbonization pilot plant in Hyderabad, the Government of India constructed a 900-TPD commercial plant in Naspur, in 1979, in the state of Andhra Pradesh.⁴⁰ The plant consists of three 300-TPD internally heated Lurgi-Spülgas type carbonizers. For the last 9 years the plant has been producing smokeless domestic fuel. At present, the condensable hydrocarbons are sold as a coal tar fuel, and a tar processing plant will be built when the capacity of the plant is increased to 2700 TPD. The char fines are briquetted, processed, and sold as additional smokeless domestic fuel. The char and condensable hydrocarbons are in great demand in the area where the plant is located. The Government of India is building a second low-temperature carbonization plant of similar capacity at Dhankuni in West Bengal. This plant will be based on an externally heated moving-bed low-temperature carbonization process.

Horizontal moving-bed processes that have been operated commercially include: the Disco process (Figure I-39), which was run successfully by the Pittsburgh Coal Carbonization Company to produce domestic fuel from Pittsburgh Seam coal until the 1950's; the Mimura (Figure I-40) and Wanishi processes, operated in Japan before and during World War II; and the Lurgi-Ruhrgas process (Figure I-41), which is still active in Germany and the United Kingdom. The latter, although classified here as a horizontal moving bed, is actually a rapid carbonization process, which combines a double-screw mixing chamber with an entrained bed to process weakly caking coal or oil shale. A demonstration plant using the Hayes process (Figure I-42) was operated by Allis-Chalmers in the 1930's to produce smokeless fuel. Pilot plants using horizontal moving-bed technology have also been built in the United States [University of Kentucky, Toscoal (Figure I-43)], and Germany (Humboldt Sand). The Toscoal project, which was recently suspended, involved the use of heated ceramic balls to bring heat to the coal bed in a reactor resembling a ball mill. Illinois No. 6 coal was used as a feedstock.

Conveyor-type moving-bed plants that have been operated in the United States include Storrs (Figure I-44), which used a moving grate to produce smokeless fuel from Utah bituminous coal; Dravo Straight-Grate (Figure I-45), which processed a pelletized mixture of bituminous coal and limestone to yield a solid boiler fuel; and Flat-Bed (Figure I-46), a pilot plant built in St. Louis in 1959 to produce industrial fuel. The Dravo process is the most

Figure I-39. CROSS-SECTION VIEW OF DISCO MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-40. CROSS-SECTION VIEW OF MIMURA MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-41. SCHEMATIC DIAGRAM OF LURGI-RUHRGAS LOW-TEMPERATURE CARBONIZATION PLANT

Figure I-42. CROSS-SECTION VIEW OF HAYES MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-43. SCHEMATIC DIAGRAM OF TOSCOAL LOW-TEMPERATURE CARBONIZATION PLANT

Figure I-44. CROSS-SECTION VIEW OF STORRS MOVING-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Figure I-45. SCHEMATIC DIAGRAM OF DRAVO STRAIGHT-GRATE LOW-TEMPERATURE CARBONIZATION PROCESS

Figure I-46. LAYOUT OF FLAT-BED LOW-TEMPERATURE CARBONIZATION REACTOR

recent, the project having been suspended in the 1970's. It is reported that a commercial-scale plant (LFC) using a rotary roof with suspended rabble arms to move the coal across a stationary grate is presently under construction in Colstrip, Montana, to process subbituminous coal into liquid fuels and char for power generation.⁷

Fluidized-Bed Processes

Fluidized-bed gas-solid contacting allows for improved mixing, heat transfer, and throughput in the mild gasification of coal. In the past, the processing of agglomerating coals required either pretreatment of the coal, dilution with some noncaking solid, or staged heating to avoid upsetting the fluidized-bed properties. However, recent research and development related to the KRW, and U-GAS coal gasification processes has demonstrated that caking coals, including the Pittsburgh seam coals, can be successfully processed at specific throughput rates of up to 1600 lb/ft²-h, in single-stage pressurized gasifiers.

The Hayashi fluidized-bed carbonizer operated commercially in Japan in the late 1950's, processing bituminous coals to yield char, tar, and medium-Btu gas. Extensive work has been done by the FMC Corporation on the COED process (Figure I-47) and related processes including COGAS, COCHAR, Seacoke (Figure I-48), and FMC Coke (Figure I-49). This family of designs uses staged fluidized beds, which allows the processing of caking coals. Several coal types have been studied, and further processing of the products have also been the subject of several studies. The FMC Coke process presently produces about 115,000 tons/year of form coke from subbituminous coal at a plant in Kemmerer, Wyoming. The product is used as a chemical reductant in the production of elemental phosphorus at Pocatello, Idaho.

The Consol process (Figure I-50) was studied at the pilot scale from 1963 to 1972, using a stirred fluidized bed to convert coal to co-products. Pittsburgh Seam coal was subjected to a solvent extraction step before feeding to the carbonizer.

The Institute of Gas Technology operated the Singh process (Figure I-51) pilot plant in 1952 to convert hvbC coal to co-products, using a three-bed system. The first fluidized bed was a partial oxidation step; the pretreated coal was then sent to the second fluidized bed where it was mixed with hot

Figure I-47. SCHEMATIC DIAGRAM OF COED FLUIDIZED-BED COAL CARBONIZATION PROCESS

Figure I-48. SCHEMATIC DIAGRAM OF SEACOKE CO-CARBONIZATION PROCESS

Figure I-49. SCHEMATIC DIAGRAM OF FMC COKE PROCESS

Figure I-50. SCHEMATIC DIAGRAM OF CONSOL FLUIDIZED-BED LOW-TEMPERATURE CARBONIZATION PROCESS

Figure I-51. SCHEMATIC DIAGRAM OF SINGH FLUIDIZED-BED
LOW-TEMPERATURE CARBONIZATION PROCESS

char and fluidized with steam. The third bed was a combustion reactor to generate the hot char for the mixing step.

Other fluidized-bed pilot plants have been built in the USA (United Engineers and Constructors, Figure I-52; Southern Research Institute, Figure I-53) and in France (Cerchar, Figure I-54) in the 1950's. Bench-scale studies on low-temperature fluidized-bed carbonization have also been done by the U.S. Bureau of Mines and by CSIRO in Australia (Figure I-55).

Fluidized-bed technology generally produces higher yields of condensable hydrocarbons than the fixed-bed or moving-bed designs. Advances in fluidization research has provided the impetus for developing processes for mild gasification of caking high-volatile bituminous coals.

Entrained-Bed Processes

In the entrained-bed design, pulverized coal is carried in a flow of entraining gas while being rapidly heated. Both upflow and downflow configurations have been used. Compared with fixed-, moving-, and fluidized-bed designs, the method provides the most rapid heating of coal. It also provides for rapid withdrawal of volatile products with minimum secondary reactions. Methods have been devised for handling caking coals in entrained-bed reactors, usually involving dilution of the coal charge with recycled char or some other diluent.

The Occidental Research Corporation Flash Pyrolysis Process (Figures I-56 and I-57) was active until recently in the United States, originally as the Garrett Flash Pyrolysis Process. Coal is entrained together with recycle char heat-carrier into a downflow reactor. Bituminous and subbituminous coals have been tested, and condensable yields have been reported up to 35% with petroleum coke as heat carrier. Increased condensable yields from subbituminous coal have also been claimed in the presence of CO_2 or steam, when compared to nitrogen. The characteristics of the condensables show a correlation between the yield and the degree of tar cracking that takes place under different operating conditions. Table I-6 showed the yields and some properties of condensables from Western Kentucky bituminous coal tested under various conditions.⁶

The U.S. Bureau of Mines operated a pilot plant using the Parry process (Figure I-58) in the 1950's. An upflow entrained bed was employed to process

Figure I-52. SCHEMATIC DIAGRAM OF UNITED ENGINEERS FLUIDIZED-BED LOW-TEMPERATURE CARBONIZATION PROCESS

Figure I-53. SCHEMATIC DIAGRAM OF SOUTHERN RESEARCH INSTITUTE
FLUIDIZED-BED PROCESS

Figure I-54. CROSS-SECTION AND SCHEMATIC DIAGRAM OF CERCHAR FLUIDIZED-BED PROCESS

Figure I-55. SCHEMATIC DIAGRAM OF CSIRO FLUIDIZED-BED PROCESS

Figure I-56. SCHEMATIC DIAGRAM OF OCCIDENTAL RESEARCH CORPORATION ENTRAINED-BED BENCH-SCALE REACTOR

Figure I-57. SCHEMATIC DIAGRAM OF OCCIDENTAL RESEARCH CORPORATION
FLASH PYROLYSIS PILOT PLANT

Figure I-58. CROSS-SECTION VIEW OF PARRY ENTRAINED-BED
LOW-TEMPERATURE CARBONIZATION REACTOR

Texas lignite; heat was provided internally by combustion of a portion of the coal feed. Tests were also conducted with bituminous coals.

Summary of Published Process Data With Emphasis on Bituminous Coal
Product Yields and Quality

Fixed-bed reactor systems, many of which are based on modified coke ovens, have been designed to use any coal particle size, since these are batch systems that necessitate some form of physical dislodging of the residual coal mass -- agglomerated or not. Some designs call for lump coal or briquettes. Moving-bed reactors generally require briquettes or larger particle sizes, although conveyor or moving grate designs can tolerate a wide range of particle sizes. Fluidized beds are limited to smaller particles, less than one-fourth inch in diameter, to accommodate the dynamic properties of the bed. Entrained beds prefer smaller particles, in the pulverized fuel size range (that is, 70% below 200 mesh).

Figure I-59 shows the char yields reported by Protopapas et al.⁷ for the various process types plotted against reactor temperature. Since the types of coal, the design of reactors, and the operating conditions vary considerably, there is a great deal of scatter in these data. In general, it can be seen that char yields at a given temperature tend to be the highest for fixed beds and lower for moving, fluidized, and entrained beds, although there is considerable overlap. For a given contacting method, the char yield decreases with increasing temperature and reaches an asymptotic value as the extent of devolatilization levels off in the region of 1300° to 1400°F. The higher yield of char in the fixed beds (slow heating/large particles) is caused by the generation of secondary char through cracking or graphitization of the heavier tar components to form carbon and light volatiles. Figure I-60 is an illustration of the progression of carbonaceous structures from coal oil to graphite under carbonization conditions.⁴¹ The degree of the progression is driven downward in the figure by conditions that favor cracking reactions, such as large particles, slow heating, the presence of active surfaces, and increased temperature.

The volatile matter of the char product was seen in Figure I-13 to decline with temperature regardless of the contacting method. This is consistent with Howard's interpretation, in which he states that the degree of devolatilization depends primarily on the maximum devolatilization temperature

Figure I-59. CHAR YIELDS FROM BITUMINOUS COALS VS. TEMPERATURE FOR FIXED-BED, MOVING-BED, FLUIDIZED-BED, AND ENTRAINED-BED CARBONIZATION

(Graphitizable precursors)

OIL	Liquid (low viscosity)
↓	
TAR	Liquid (high viscosity)
↓	
PITCH	Solid (glassy)
↓	
MESOPHASE	Solid (glass with orientational order)
↓	
CARBON	Solid (paracrystalline, turbostratic)
↓	
SYNTHETIC GRAPHITE	Solid (polycrystalline)

Figure I-60. PROGRESSION OF CARBONACEOUS MATTER FROM COAL OIL
TO GRAPHITE⁴¹

attained, regardless of the heating rate.¹ Other effects on the char quality were discussed previously, in the sections on fundamental coal devolatilization studies. The heteroatom content of the char was seen to decrease with increasing temperature and residence time.

The physical properties of char are also dependent on the process conditions, particularly the rate of heating. Rapid heating, with the attendant rapid expansion of escaping volatile matter while the coal is in the plastic state, produces a porous, expanded char particle that has a higher surface area, and thus is more reactive than char produced at a similar set of conditions under slow heating. Photomicrographs of chars produced under three rates of heating were displayed in Figure I-17. The chars produced in fluidized or entrained beds display the characteristics typical of a high heating rate, that is, reduced particle density, higher surface area, and a characteristic "cenosphere" structure.

The condensable hydrocarbon yields from the bench-scale to commercial-scale processes surveyed vary considerably, due to differences in process conditions as well as the differences in measuring and reporting the yields. Figure I-61 shows that no clear trend appears from the entire data from the 36 coal carbonization processes reviewed (from Table I-11), when the tar/oil yields are plotted as a function of temperature. The yields varied from 2% to 33%, with an average value of 11.6%. More useful data on condensable yields have been obtained from laboratory studies under controlled conditions, as previously discussed. Maximum tar yields from bituminous coals have generally been observed to take place in the region of 1100° to 1300°F (593° to 704°C), although in most cases the liquid yield reaches an approximate plateau in this region. Increased pressure has a suppressing effect on tar yield, except in the presence of a substantial concentration of hydrogen, which tends to increase yield by stabilizing reactive species. It has been established that char, due to its high active surface area, promotes the cracking of tars in the presence of inert gas. The work at Occidental^{6,31} identified how rapid-rate heating and the use of reactive gases could be used to minimize this secondary decomposition. Rapid heating techniques produce the highest tar yields obtainable to date, due to the suppression of secondary decomposition reactions; the tars thus produced resemble the original coal structure more closely than conventional low-temperature tars, yielding more pitch and

Figure I-61. TAR/OIL YIELDS FROM CARBONIZATION OF BITUMINOUS COALS IN FIXED, MOVING, FLUIDIZED, AND ENTRAINED BEDS

containing a higher proportion of heteroatoms. These tars have proven difficult to hydrotreat for substitute fuel production, and may be more useful as a source of nonfuel materials (chemicals, binders, engineering materials) through a series of fractionation procedures.

The gas-phase product from a mild gasification process will vary, depending on the introduction of gases to the reactor system. The use of recycled fuel gas, flue gases, steam, or air will strongly influence the quantity and heating value of the gas produced. Figure I-62 plots the heating value of the product gas against temperature for the processes listed in Table I-10 which employ external heating. The calorific value of the product gas clearly declines as the temperature is increased. Referring to Figure I-11, methane evolution at lower temperature will gradually be replaced by H_2 and CO_x evolution as temperature increases, although this pattern is strongly dependent on the rank of the parent coal, as well as the degree of tar cracking that occurs. Since low- to medium-Btu fuel gas at low pressure is a low-value product, it is best utilized as an in-plant energy source, and conditions that tend to favor the conversion of liquid products to gases (that is, slow heating, high pressures, high temperatures) should be minimized.

Comparison to Oil Shale Conversion Processes

It is apparent that retorting of oil shale to produce condensable hydrocarbons and fuel gas is conducted at operating conditions similar to those visualized for mild gasification of coal. Extensive research and development were conducted during the 1970's to advance shale retorting to produce substitute fuels. However, the recent decline in crude oil prices has considerably slowed down this effort. Because of the similarities between mild gasification and shale retorting, the latter was reviewed to determine whether existing technologies may be suitable for, or could be modified for, application to advanced mild coal gasification. A summary of the oil shale retorting processes and their status, extracted from a recent IGT report to the International Gas Union, are summarized in Appendix A. In the past, oil shale retorting technologies have been applied to coal carbonization processes such as the Toscoal and Rexco processes, both of which employ slow heat-up methods. In general, the current large-scale operations, such as the Union Oil of California's process, the Soviet Union's Kiviter retort, the Lawrence Livermore Laboratory's process, and the Peoples Republic of China (PRC)

Figure I-62. PRODUCT GAS HEATING VALUE AS A FUNCTION OF TEMPERATURE FOR COAL CARBONIZATION IN EXTERNALLY HEATED FIXED, MOVING, AND FLUIDIZED BEDS

retort, all employ countercurrent gas-solid contacting methods, which are the PRC retort all employ countercurrent gas-solid contacting methods, which are known to be slow heat-up processes that are well suited for substitute liquid fuel production. Since the market assessment study has indicated that with the soft oil prices, the value-added benefits for the coal-derived products can be found for specialty chemical feedstocks such as pitch, creosote oil, naphthalene, and form coke, it is decided to adopt a rapid coal heat-up technique for the conceptual mild gasification process. Besides, the emphasis of this study being on the utilization of the caking eastern high-volatile bituminous coals, the moving bed and the rotary reactors that were successfully applied to shale retorting are considered to be unsuitable for processing caking coals. Consequently, no further efforts were made to study the principles and applications of the shale retorting know-how to mild gasification.

Conclusions Leading to the Selection of a Range of Operating Conditions and Reactor Design Criteria

The selection of process conditions is dependent upon the desired product slate. Slow heating will favor cracking of the condensable hydrocarbons, thus producing more fuel gas, more char, and a condensable product that resembles low-temperature tar, such as that produced by the Coalite process.²⁸ On the other hand, rapid heating favors the conservation of primary tars thus resulting in a higher yield of condensables that resemble tar from the Occidental Research Corporation Flash Pyrolysis Process.⁶ Table I-11 shows a comparison of typical products from these two processes. It is evident from this table that aromatics can be selectively produced by rapid heating of coal.

Eastern bituminous coals have been found to produce the highest yields of condensable hydrocarbons upon devolatilization. The Eastern coal basins with the most extensive reserves are closest to the major population centers of the Eastern United States. Since these coals contain high sulfur levels, they are becoming increasingly difficult to market as utility boiler fuel without extensive chemical treatment for environmental reasons. If these coals can be utilized in an environmentally acceptable manner, they will become prime candidates for mild gasification; however, the gases, liquids, and char products will contain significant quantities of sulfur.

Table I-11. COMAPRISON OF TYPICAL CONDENSABLES FROM COALITE AND OCCIDENTAL FLASH PYROLYSIS

<u>Property of Tar</u>	<u>Process</u>	
	<u>Coalite²⁸</u>	<u>Occidental⁶</u>
Run No.	NA	175
Yield, wt % dry coal	9.0	25.0
Specific Gravity	1.029	1.143
Moisture, wt %	2.2	(maf)
Ash, wt %	0.1	(maf)
Elemental Analysis	<u>maf wt %</u>	
C	84.0	78.8
H	8.3	7.1
S	0.74	1.7
N	1.08	1.8
O	5.78	10.6
H/C Atomic Ratio	1.18	1.07
Toluene-Insolubles	1.2	18.0
Distillation Range, °F	<u>Cumulative wt %</u>	
≤550	44	~10
551-580	67	~25
680-end point	NA	~49
Total Pitch (wt % of tar)	26.0	53.3

In the literature, frequent mention is made of comparing the "quality" of devolatilization liquids from various types of experiments at different sets of conditions. Often, the meaning of the term "quality" is determined by the goals of the project rather than by an objective criteria. Since the majority of coal devolatilization investigations, other than those aimed at acquiring fundamental coal chemistry information, have been tied to the common goal of producing substitute fuels from coal, this has been the basis of a subjective evaluation of the quality of condensables produced. The condensables of "high quality" are often considered to be those with high H/C ratio and low molecular weight, because these properties reduce the requirement for further upgrading to liquid fuel feedstocks. However, this viewpoint may be

misleading if the goal of the investigation is to produce a product slate that can show the potential value-added benefits in the current market.

Prior to the Second World War, coal was the primary source of many carbon-based chemicals, as well as fuel forms. The post-war shift to petroleum-based chemistry, combined with the dwindling availability of coke-oven by-product tars, resulted in the decline of coal-based products in the marketplace. However, the products that can be made from coal via mild gasification include some which may command market prices exceeding their fuel value, if the markets can be shown to be sufficiently large and accessible. These products, which will be discussed in more detail under Subtask 1.2, include phenols, BTX, creosote oils, and pitch. With this in mind, the "quality" of the condensable devolatilization products takes on a different meaning, and products that may have been labeled as "inferior" under previous studies must be reevaluated.

The temperature range, which can be defined as "mild," covers a range of about 900° to 1500°F (482° to 816°C). Below this temperature, coal devolatilization is limited and slow in the absence of catalysts, solvents, high-pressure hydrogen, or some form of chemical pretreatment to yield appreciable quantities of high-value products; above this range, devolatilization is essentially complete, and further conversion of coal carbon necessitates the pursuit of more severe steps such as steam-oxygen gasification or CO₂-oxygen gasification. In the devolatilization temperature range, there is also a degree of flexibility regarding the product slate; for example, phenol yields are favored by lower temperatures, and pitch yields are favored by higher temperatures.

The pressure range for mild gasification will be restricted to the lowest practicable pressure for the reactor system chosen, since the favorable effects of increased pressure⁴² in the presence of reactive process-derived fuel or flue gases do not appear to be appreciable in the temperature range chosen.

The fuel gas produced by the process, together with hot flue gases produced by combustion of coal, char, excess fuel gas, or some combination of all three, provides a convenient source of reactor gas medium which may enhance tar yields when compared with inert gas. This gas mixture would

contain H_2 , CO , CO_2 , H_2O , CH_4 , and other hydrocarbons, of which H_2 , CO_2 , and H_2O would be expected to favorably affect the product yield and distribution.

As will be discussed later, process conditions that favor maximum yield of condensables within the range of conditions defined as "mild gasification" appear to be the most technically and economically promising. For this reason, a reactor system that uses small particle sizes and rapid heating rates will be selected as a candidate for process development. The use of sulfur-capture additives, possibly lime or siderite, will be reserved as an option, depending on the sulfur content of the products and their end uses, and also on the effects of the additive on the yield of condensable products and sulfur content of char. The know-how exists⁴³ to process caking coals without oxidative pretreatment by maintaining an inventory of diluent char in the fluidized bed.

The KRW and U-GAS processes were able to feed highly caking Pittsburgh Seam coal into fluidized-bed reactors of 12-inch and 8-inch ID, respectively. During the development of the U-GAS process at IGT, it was learned that feeding caking coals was easier when the atmospheric-pressure 3-ft-ID PDU was operated, compared to the high-pressure 8-inch-ID PDU.⁴⁴ Hence, the operation of conceptual commercial reactors, with estimated diameters of up to 12 feet, with caking coals should be much less difficult than conducting laboratory or PDU tests with these same coals.

Steam pretreatment of the coal will also be reserved as an option for study to further improve liquid yields.

It is apparent from reviewing the various types of mild carbonization processes that the existing technology is not deriving the benefits expected for an advanced mild gasification process. The fixed- and moving-bed reactor processes employ large particles and slow heat-up rates. Even though the reactors are simple in design their cyclic operation is cumbersome, and they may have to be significantly modified to meet New Source Performance Standards (NSPS). Processes that burn condensable volatiles are unsuitable to achieve the goals of mild gasification. Most of the commercial fluidized-bed reactor processes inject air into the reactor to supply the energy for coal devolatilization at the cost of condensable hydrocarbons productions. Fluidized-bed processes that employ a recirculating stream of inert solids or char are complicated in design and operation. The entrained-bed processes have the

disadvantage of requiring finely ground coal with the associated risk of contaminating the condensables with carry-over char fines. The Occidental entrained pyrolysis process, operating without an oxidant in direct contact with the feed coal, meets most of the mild gasification process requirements. As stated earlier, it requires fine grinding of coal, may result in high carry-over of char fines, and, also, the commercial designs show heat being supplied to the feed coal by circulating partially combusted char. Based on these observations, it is concluded that an advanced reactor design, capable of processing all types of coal -- coarse and fine coal particles at rapid heat-up conditions -- preferably without a circulating char stream, and introducing little or no oxidant into the reactor, is worthy of development. An advanced reactor system of this type will not only maximize the condensable hydrocarbons yields, but also will operate continuously at high throughput rates.

20WP/61089trl/RPP

Subtask 1.2. Literature Survey of Char, Condensables, and Gas Upgrading and Utilization Methods

Objective

The objective of this task is to review the properties of char, condensable hydrocarbons, and gases produced by the mild gasification of typical bituminous coals; identify potential areas for their use; and examine possible ways in which these products may be improved to make them attractive to potential users.

Char Upgrading Methods

The properties of the char will depend on the characteristics of the parent coal, the severity of the mild gasification employed, the physical sizing of the coal feed, and the changes in particle size and surface characteristics occurring during gasification. Potential uses of the char will depend on its properties and the degree to which these properties can be economically improved through upgrading treatments.

Char Properties and Product Specifications

The char properties influencing its potential use are: chemical composition, gross particle size distribution, and surface characteristics, as influenced by internal pore volume/area and surface reactivity. Other properties such as mechanical strength, bulk density, and combustion reactivity are also important in meeting specific storage, handling, and use requirements. Because of the variable nature of the parent coal, these properties will not be constant and indeed will show wide variation.

Char product specifications reflect this variability and have been developed on the basis of market requirements. For example, the most widely used char product is metallurgical coke. The specifications reflect a compromise between properties desired by the user industry and those economically attainable with available feed coal blends and coke-making processes.

Table I-12 illustrates the properties of chars derived from two severities of fluidized-bed mild gasification for each of three typical high-volatile bituminous coals.^{14,45} The table shows the expected increase in ash content and sulfur content on a Btu basis, as well as a reduction in size of the char.

Table I-12. CHARS FROM MILD GASIFICATION OF MIDWESTERN COALS^{14,45}
(Illustrated by Chars From the 2nd and 3rd Stages of FMC COED Fluidized Bed Process)

	Illinois No. 6			Western Kentucky No. 9 and No. 14			Pittsburgh No. 8		
	Stage 2		Stage 3	Stage 2		Stage 3	Stage 2		Stage 3
	Coal	Char	Char	Coal	Char	Char	Coal	Char	Char
Moisture, wt %	9.0*	1.1	0.9	3.5*	1.1	1.1	1.8**	0.1	0.2
Proximate, wt % (dry)									
VM	38.5	12.1	9.3	38.0	13.8	10.9	38.3	23.8	10.6
FC	50.0	61.6	67.6	53.3	73.4	73.0	52.7	66.5	76.9
Ash	11.5	26.3	23.1	8.7	12.8	16.1	9.0	9.7	12.5
Ultimate, %									
C	67.3	63.9	63.8	70.3	74.8	74.1	73.0	73.8	75.3
H	4.9	1.8	1.1	5.2	2.5	2.0	5.2	3.8	2.8
N	1.3	1.1	0.8	1.5	1.5	1.6	1.3	1.3	1.4
S	4.3	4.6	6.3	3.1	2.9	3.3	4.3	4.1	4.0
O	10.7	2.3	0.0	11.2	5.5	3.0	7.2	7.3	4.0
Ash	11.5	26.3	28.0	8.7	12.8	16.0	9.0	9.7	12.5
HHV Btu/lb (dry) (calculated)	12,230	10,300	10,060	12,990	12,240	12,010	13,460	13,190	13,300
Density, lb/ft ³	48.8	27.5	27.5	45.5	29.3	31.3	N/A	24.8	23.8
Size Const., cumulative % Tyler Mesh									
14	20.2	9.0	3.7	10.1	4.0	3.5	13.2	6.1	12.2
28	57.2	37.7	40.0	35.2	37.4	35.6	42.9	36.3	50.3
48	75.9	66.0	67.9	57.0	67.8	66.7	64.6	57.5	70.5
100	86.2	84.4	83.1	73.0	86.4	85.2	79.0	74.0	81.5
200	92.2	94.3	92.4	85.1	94.4	93.5	82.6	85.0	85.6
325	95.2	97.7	96.1	92.1	97.8	97.4	93.4	93.8	93.7
Pan	99.7	99.8	99.6	100.0	100.0	100.0	100.0	100.0	100.0
Avg. Process Temp, °F	--	800	990	--	765	885	--	725	840

* As fed to Stage 1.

** As received.

For comparison, Table I-13 illustrates the properties of a typical coke (char) intended for blast furnace reduction of iron ore. In comparing these mild gasification chars and the metallurgical-grade coke, the most noticeable characteristic is the higher sulfur and ash contents of the mild gasification char, which reflects the corresponding assay of the feed coals. In addition, there are marked differences in physical form between the low-density, small particle-size char and the high-density, high-strength coke. Converting the char to form coke will improve the physical properties of the mild gasification char; however, the high sulfur content may require lime addition, either to the blast furnace or to the molten metal, to avoid sulfur contamination of the iron. If lime is used as a sulfur-capture additive in mild gasification, the form coke made from the lime-char mixture will have the inherent capability to absorb the residual sulfur contained in the char.

Table I-13. CHARACTERISTICS OF BLAST FURNACE COKE

Property	Metallurgical Coke		
	I 3.0 in.	II 2.5 in.	III 1.5 in.
Tumbler Strength, %*	85	85	85
Abradability, M_{10} , %*	6	6	6
Moisture, % of raw product	1.5 ± 0.5	2.5 ± 0.5	3.5 ± 0.5
Ash, %	8.5 ± 0.3	8.5 ± 0.3	8.5 ± 0.3
Sulfur, % of dry product	0.9 ± 0.03	0.9 ± 0.003	0.9 ± 0.03
Volatile Matter, % of dry product	less than 1	less than 1	less than 1
Alkali, % of dry product**	0.26	0.26	0.26
Bulk Density, lb/ft ³	--	--	27

* According to DIN 51 717, conforming with ISO/R-1967.

** Content of Na_2O and K_2O determined in different plants.

Char produced for different end uses will have requirements which reflect the historical requirements for the particular use. For a number of these end uses, an upgrading of the gasification char through reduction in sulfur and ash content, adjustment of particle size, etc., will be required. Potential methods for upgrading char are described in the following section.

Conventional Upgrading Technologies

Upgrading requirements for the char parallel those normally employed for improving the quality of the parent coal. These include concentration of the carbonaceous material by the rejection of mineral matter (ash), reduction in sulfur content (generally inorganic sulfur), and adjustment of particle size and distribution.

The as-mined coal will normally contain rocks, soil, and other mineral diluents. These are customarily separated by crushing and screening the coal and subjecting the sized material to a mineral removing step. Conventionally, this step could involve either gravity separation or flotation. In gravity separation, the difference in specific gravities of coal and minerals is utilized to separate the two. Flotation makes use of surface property differences, coal being generally hydrophobic and minerals hydrophilic.

Gravity Separation Methods

Gravity separation methods may be classified under two general groupings: those that use water and those that use a higher specific gravity medium. The latter group is also known as heavy-medium or dense-medium separation. The heavy medium usually consists of a suspension of finely ground solids in water. Magnetite, with its high density and magnetic properties favoring its near complete recovery, is the most common choice for the preparation of the heavy medium.

Flotation

This is a method in which air bubbles are introduced and made to attach to the coal particles, thus reducing their effective density and allowing them to separate (float away) from the heavier minerals.

These conventional cleaning methods are generally effective in reducing the mineral content of coal. They are less effective, however, with char. This is due in part to the change in surface properties of the char with respect to the coal and because of the tendency for caking coals to become plastic during heating and encapsulate the mineral particles within the carbonaceous residue. In addition, these physical separation methods, which reject mineral-phase sulfur (pyrites), do not reject organic sulfur within the coal. The organic fraction of the sulfur in coal could constitute as much as 50% of the total sulfur.

Advanced Upgrading Technologies

Several advanced technologies for upgrading coal to reduce its ash and sulfur content are now being vigorously researched by various national and international organizations. Some of the noteworthy processes are as follows:

- Selective agglomeration
- Advanced dense-medium processes for fine coal, also known as true liquid gravity separation
- Advanced flotation-microbubble flotation, column flotation, etc.
- Selective flocculation
- Electrostatic separation
- High-gradient magnetic separation
- Chemical coal cleaning processes
- Ultra-high-temperature pyrolysis.

The following paragraphs describe the processes, discuss their status of development, and discuss potential limitations for both coal and char upgrading.

Selective Agglomeration

Coal particles are water-repellant, but show an affinity to oil or other liquid hydrocarbons. Vigorous agitation of a coal-water slurry containing immiscible hydrocarbon results in the collision of hydrocarbon-coated coal particles to form flocs or agglomerates, with the hydrocarbon acting as the bridging fluid.

This process, termed spherical agglomeration, has been proven to be effective in recovering fine coal including ultra-fine particles. The clean product is relatively free of water, as water is also separated by evaporation if a thermal hydrocarbon recovery step is used. Economical hydrocarbon recovery is a requirement of the process.

The technology was originally developed using a heavy petroleum product as the bridging liquid.⁴⁶ Recovery of the heavy oil was not practical and it therefore was left in the coal product. With the rise in oil price relative to coal, recovery and reuse of the oil is required. A modified process using lighter hydrocarbons (such as heptane) for the primary flocculation is

expected to facilitate hydrocarbons recovery, minimize its loss, and improve the processes economic viability.⁴⁷

The selective agglomeration process has proven to be very effective for nearly total rejection of the ash portion that is not encapsulated with coal matter; ash contents as low as 2% have been achieved. The tailings comprise close to 95% of noncombustibles, indicating a nearly total energy recovery in the saleable product. Selective agglomeration coupled with froth flotation can reject all separate mineral particulates, including the fraction of sulfur-containing pyrites which are contained externally to the coal particles. The technology is not useful for the reduction of organic sulfur, which can account for 50% of the total sulfur in the raw coal.

The National Research Council (NRC) of Canada has developed the process of selective agglomeration and tested it through pilot plant scale. The Arcanum Corporation of Ann Arbor, Michigan, has the NRC license for use of the process in the United States. Bechtel National, Inc., in cooperation with Arcanum, is testing the process under a current DOE-funded program.

Bechtel/Arcanum have proposed a two-stage approach that uses heptane in the first stage to make micro-agglomerates. In the second stage, the micro-agglomerates are enlarged using a low shear mixer and a heavy oil binder. The heptane is recovered by evaporating and condensing the vapors. The binder remains with the product cleaned coal.

It is doubtful that this process will be directly applicable for char upgrading, because the process depends heavily on the natural hydrophobic surface characteristics of coal. When the coal is devolatilized, the resulting char particles may no longer exhibit the required hydrophobicity. The process is, however, applicable to precleaning of the coal prior to its mild gasification.

Advanced Dense-Medium Separation

Dense-medium processes have been applied extensively in the coal preparation industry, and have proven to be flexible and effective for gravity separation of coal from the heavier mineral matter. For coarse particle sizes (+1/4-inch size), dense-medium vessels are used. For particle sizes down to 100 mesh, dense-medium cyclones that increase gravitational forces to accelerate the separation of fine particles are employed. However, as the

size of the particles to be treated approaches the size of the magnetite particles (325 mesh X 0) used to formulate the dense medium, an effective separation can no longer be made. Therefore, in recent years, interest has grown in replacing the magnetite-water medium with a heavy liquid (organic liquid or homogeneous aqueous solution with a specific gravity in the range of 1.2 to 1.9) so that the use of cyclones can be further extended to clean particles down to zero size. Heavy-liquid cycloning refers to the centrifugal separation of coal from mineral matter and pyrite by exploiting differences in their specific gravities using a true heavy liquid rather than a suspension.

This technology is still in the pilot-plant stage.⁴⁸ The recovery of solvent used as the cleaning medium and safety in solvent handling are critical items of concern.

With respect to the extent of upgrading, this process could be comparable to microbubble flotation, even though the operating principle of the dense-medium process is based on specific gravity rather than surface characteristics.

For applicability to char, data specific to the char would be needed, since particle densities may be altered during mild gasification. Unless data for a specific char sample indicate potential of specific gravity separations as a viable option, this process has to be ruled out for the general run of chars.

Advanced Flotation

Most of the advanced flotation processes currently under development use microbubble technology. Microbubble flotation is a further development of conventional froth flotation. Flotation of coal, as currently practiced, uses large mechanically agitated cells. These cells exhibit poor selectivity for particles sizes below 100 mesh. In the production of ultraclean coal, ash liberation requires the coal to be ground to the ultra-fine range. Ultra-fine coal flotation requires extremely small bubbles and a means to impart adequate forces at the bubble-solid interface to produce coal-to-bubble attachment.

A study at Bergbau-Forschung⁴⁹ has resulted in the development of large-capacity pneumatic microbubble cells with several unique features in bubble generation, coal-to-bubble attachment, separation of froth and slurry, froth removal, etc. A 1-TPH proof-of-concept plant was recently tested at the EPRI

coal cleaning test facility at Homer City, Pennsylvania, by Bechtel National, Inc.⁵⁰

The microbubble process using the Bergbau-Forschung machine has been operating successfully since 1982 in Germany. It performs well with coal particles below 9 microns in size. Coupled with the ability to selectively separate ultra-fine coal and refuse materials, microbubble flotation lends itself to improvement by use of developing techniques in pyrite suppression and "reverse" flotation.

The equipment and the reagents used in microbubble flotation are both relatively inexpensive. Energy consumption is well within acceptable limits. Unit capacities up to 20 TPH are currently available and have been operated successfully for less severe cleaning operations, yielding a product with up to 8% ash. Designs have been developed for deep cleaning (2% to 4% ash); however, energy recovery levels at low ash levels is extremely coal-specific. For the Midwestern coals considered (Pittsburgh No. 8 and Illinois No. 6), clean coal at 4% to 5% ash can be produced at acceptable energy recovery levels (80% and higher) with a significant reduction in the pyrite sulfur. It is recommended that this advanced technique be used on coals after their initial treatment in a conventional plant to remove mine rock and easily removed impurities.

There are no data on the applicability of microbubble flotation to char; however, it is doubtful that this process, which also uses the hydrophobic surface characteristics of coal, will be directly applicable to char. In fact, even for coals with partially weathered particle surfaces, the effectiveness drops steeply.

Selective Flocculation

Flocculants have been identified by Battelle Columbus⁵¹ that preferentially and selectively flocculate coal in the presence of minerals, including pyrite. Research is being continued by Ohio State University.⁵² Basically, the process follows four steps:

1. Dispersion of coal and mineral matter with surfactants
2. Addition of polymers that selectively attach themselves to the coal particles and flocculate them

3. A conditioning step in which the flocculated coal particles are allowed to grow in size, thus enhancing their settlement in the next step
4. Separation by settling.

The flocs are relatively fragile and may contain trapped mineral particles.

Researchers report encouraging results with selective flocculation. Consumption of flocculants is relatively low, since the particles do not have to be coated with the reagent. Point contact of the particles with the molecular strings are sufficient. Several flocculants have been identified that selectively react with coal particles. However, tests have been limited to the bench scale, and the process has not been operated continuously.

The use of flocculants to enhance settling of solids is not new, but it remains a very complex art. The effect of the flocculants is highly dependent on the chemical and physicochemical system presented by a coal-mineral-water mixture, which is subject to constant change. Researchers are still not completely certain that all the phenomena affecting flocculation have been understood. This is confirmed by the experience that it is very difficult to maintain the process balance in the conventional clarification systems employed in coal-cleaning plants. Control is currently maintained by trial-and-error adjustment of reagent addition and pH control.

The four required process steps previously described underline the sensitive nature of the process. Whereas the first three steps require relatively simple process equipment such as tanks and agitators, the fourth step, separating the flocculated coal, may require development of special equipment for settling and thickening. Regardless of equipment used, flocculated coal product will contain a relatively large amount of water and trapped minerals. High separation efficiency may require a two-stage cleaning with repeated destruction of the flocs and dilution with fresh water. This process is still in its infancy, although claims indicate that selective flocculation could be as effective as advanced flotation for some coals.

No data are currently available on the applicability of selective flocculation to coal char; however, the dependence of the process on the surface characteristics of coal and associated minerals implies that performance with char would be impaired.

Electrostatic Separation

This is a dry process for which moist coal fines would require drying before treatment. The process depends upon the difference in electrostatic behavior (attraction/repulsion) of mineral and coal particles when subjected to electrostatic charge. The process is still in the laboratory stage.⁵³ The effectiveness of this process with char is unknown, as no test data appear to have been published. However, the dry nature of the char should be an advantage, although the drying of coal fines involves a potential explosion and fire hazard.

High Gradient Magnetic Separation

High Gradient Magnetic Separation (HGMS) is a process that uses magnetic solids separation technology to clean coal. HGMS can be used to separate weakly magnetic as well as strongly magnetic solids down to extremely fine particle sizes, in the micron range. Coal pyrite sulfur and commonly associated amounts of mineral impurities are magnetically distinguishable from pure coal. If these magnetic particles can be "liberated" and made to form discrete particles by fine grinding, there is a good possibility of separating them using HGMS. The process, applied to wet coal slurry, has been tested at the pilot plant scale. It appears to have potential for selective removal of pyritic sulfur. The potential for direct upgrading of char by this method does not appear attractive, however, because of the failure to remove organically bound sulfur and because of the probable encapsulation of mineral matter during the coal devolatilization.

Chemical Coal Cleaning

Chemically based processes have been investigated as a means to reduce both pyritic and organic sulfur in coal. For most processes, no significant removal of ash components is attained. Processes based on chemical attack on the coal matter may be effective for char as well as coal upgrading.

The following list summarizes a number of illustrative processes evaluated under a prior DOE program:⁵⁴

- Pittsburgh Energy Technology Center (PETC)
- Ledgemont
- Ames Laboratory

- Jet Propulsion Laboratory (JPL), two versions of the process
- Guth Process (KVB).

The operating principles and characteristics for these six process concepts are compared in Table I-14.

Coal preparation prior to chemical cleaning normally includes the physical cleaning of all size fractions and size reduction by wet or dry grinding. The major points developed in the assessment are summarized as follows.

Three of the processes examined use a similar oxidation method to reduce sulfur content. PETC, Ledgesmont, and Ames processes are based on the general unbalanced reaction:

FeS_2 represents both mineral and organic sulfur content.

The PETC process uses compressed air as a source of oxygen. The Ledgesmont and Ames processes employ oxygen. Reactions in the three oxidation processes are exothermic, and sufficient heat is created to maintain conditions in the reactor.

The two JPL processes use chlorine gas as the sulfur-removing agent. The separate processes, JPL-1 and JPL-2, differ from each other in that the earlier JPL-1 process used methylchloroform as a coal transport fluid; the later JPL-2 process uses water.

The Guth process (KVB) uses gaseous nitrogen dioxide in the presence of oxygen to remove sulfur. Recovery of the chemicals used in the JPL and Guth processes are important design requirements.

All of the above processes require considerable engineering development, and all are projected to cost from \$35 to \$50 per ton of coal cleaned (expressed in 1980 dollars). The application of these processes to sulfur removal from char appears possible, but would have to be verified for a specific char.

Recent work reported under DOE Contract Number DE-AC21-87MC23290 by UCC Research Corporation⁵⁵ claims deep removal of both ash and sulfur from char when treated with chlorine gas at temperature ranging from 2000° to 3000°F.

Table I-14. COAL CLEANING PROCESSES: PROCESS CONDITIONS AND ILLUSTRATIVE PERFORMANCE

Process Characteristics	PETC	Ledgemont	Ames Laboratory	JPL-1	JPL-2	Cuth Process (KVB)
Chemical Reaction	$\text{FeS}_2 + 15/4\text{O}_2 + 2\text{H}_2\text{O} \rightarrow 1/2\text{Fe}_2\text{O}_3 + 2\text{H}_2\text{SO}_4$	$\text{FeS}_2 + 7/2\text{O}_2 + \text{H}_2\text{O} \rightarrow \text{FeSO}_4 + \text{H}_2\text{SO}_4$	$2\text{FeS}_2 + 15\text{Cl}_2 + 16\text{H}_2\text{O} \rightarrow 1/2\text{Fe}_2\text{O}_3 + 2\text{H}_2\text{SO}_4 + 24\text{HCl}$	$2\text{FeS}_2 + 15\text{Cl}_2 + 16\text{H}_2\text{O} \rightarrow 2\text{FeCl}_3 + 4\text{H}_2\text{SO}_4 + 24\text{HCl}$	Same as JPL-1	$\text{FeS}_2 + 6\text{NO}_2 \rightarrow \text{FeSO}_4 + \text{SO}_2 + 6\text{NO}$ and $6\text{NO} + 3\text{O}_2 \rightarrow 6\text{NO}_2$
Reactor Condition	Acid	Acid	Basic	Acid	Acid	Acid
Reaction Temperature	200°C	200°C	150°C	70°C	70°C	100°C
Reaction Pressure	6900 kPa	2070 kPa	2070 kPa	Atmospheric	Atmospheric	Atmospheric
Reaction Time	1 hour	1 hour	1 hour	45 minutes	45 minutes	1 hour
Pyritic Sulfur Removal	95%	95%	95%	80%	90%	100%
Organic Sulfur Removal	20%	20%	20%	40%	20%	30%
Coal Recovery at Dryer ^a	90.5 wt %	90.5 wt %	90.9 wt %	91.8 wt %	96.7 wt %	97.9 wt %
Coal Use for Utilities ^a	10.3 wt %	9.1 wt %	3.7 wt %	21.7 wt %	13.0 wt %	3.0 wt %
Net Production ^a	80.2 wt %, 267.3 TPH	81.4 wt %, 271.5 TPH	87.2 wt %, 290.6 TPH	70.1 wt %, 233.6 TPH	83.7 wt %, 279.1 TPH	94.9 wt %, 316.3 TPH
Coal Slurry Concentration	20% Coal - 80% Water	20% Coal - 80% Water	20% Coal - 80% Water	33% Coal - 67% Methylchloroform	33% Coal - 67% Water	Dry Process
Grinding Method	Wet	Wet	Wet	Dry	Dry	Dry
Coal Size	70-80% - 200 mesh	70-80% - 200 mesh	70-80% - 200 mesh	70-80% - 200 mesh	70-80% - 200 mesh	-14 mesh
Oxidizing Gas Feed Basis	2 X Stoichiometric	2 X Stoichiometric	2 X Stoichiometric	Stoichiometric Plus 10%	Stoichiometric Plus 10%	2 X Stoichiometric
Other Major Chemicals Used	--	--	Na_2CO_3	$\text{Cl}_2, \text{CH}_2\text{Cl}_3$	Cl_2	NO_2, NaOH

^a Dry basis; 333.3 TPH feed to all processes.

20WP/61089T2-3/RPP

The practicality and economics of such a process remains to be demonstrated. In the most recent development of the TRW Inc. Gravimelt process, coal is treated with a 50/50 mixture of sodium and potassium hydroxides at temperatures of 1300° to 1355°F for approximately 3 hours. Nearly 90% of the total sulfur and more than 95% of the total ash is removed. The sulfur and mineral matter are converted to water-soluble compounds during the caustic treatment step.⁵⁶ It is conceivable that the mild gasification char could be desulfurized in a similar manner. This process is still under development.

As described by U.S. Patent No. 4,188,191, Longanbach and Robinson have invented a total desulfurization scheme that operates by contacting char with molten caustic.

Exposure of an Illinois No. 6 mild gasification char to further devolatilization in a fluidized bed in contact with steam was shown to result in a reduction in char sulfur content to about 0.7% by weight, down from 1.61% by weight as reported for devolatilization at 1100°F without steam. These results were obtained in bench-scale studies carried out by Westinghouse under EPRI sponsorship.⁵⁷ Other notable desulfurization schemes include the extensive hydrosulfurization of coal chars during 1965 to 1974, and the development of the Meyers process to desulfurize coal.

Ultra-High Temperature Pyrolysis

Heating coal or char to extremely high temperatures (>2000°F) results in almost complete liberation of coal volatile matter, and, along with it, sulfur derived from both mineral and organic coal constituents.

Summary of Char Upgrading Methods

Although selective chemical cleaning processes may be applicable for reducing ash and sulfur content of chars, such processes generally entail either prohibitive costs and/or have limited ash removal capability.

The preferred route to ash rejection appears to be advanced physical cleaning techniques applied to the coal prior to the mild gasification step. The treating scenario illustrated in Figure I-63 is suggested based on published information on float-and-sink data for Midwestern high-sulfur coals.

The size consist of the product char from mild gasification will depend on the feed coal sizing requirement and the mild gasification process

A88010022P

Figure I-63. ADVANCED FEED COAL CLEANING CONCEPT FOR ASH AND MINERAL SULFUR REDUCTION

selected. For some end uses, or for shipping convenience, a larger and more uniform char-size may be required. This may be obtained by briquetting or pelletizing the char using standard equipment and methods. Blending washed coal with the hot char may assist in the briquetting, which could be supplemented, if required, with tar or pitch separated from the recovered condensables, or even petroleum pitch, in case the coal-derived pitch has a higher market value.

Some end uses of the char may require further size reduction by fine grinding or pulverizing. These are standard processes, although some adaptation may be needed to accommodate the potentially flammable hot, dry char.

The mild gasification of coal will develop some porosity in the product char to a degree that will depend on the parent coal and the processing conditions. The surface characteristics and reactivity of the product char can be modified by reaction of the hot char with steam or other reactant. Increased pore volume and surface area may be desirable and may suit the char for use as a low-cost activated carbon. As indicated in this discussion of chemical cleaning, reactions of the char with steam may also serve to remove additional bound sulfur.

Char Utilization Methods

The char product from mild gasification contains about 60% to 80% of the feed coal heating value. For this reason, its disposal through sales to an end user is critical to the economic viability of any mild gasification project.⁵⁸

The following discussion identifies present and potential end uses into which the char could be sold. The Subtask 1.3 Market Assessment report discusses the potential value-added uses for the char in the present market.

Although, as discussed in the prior section, it is possible to upgrade the char by chemical or steam treatment to reduce char sulfur content, most upgrading would significantly increase the costs of the char. The following sections discuss the potential uses for the char as they relate to the char properties.

Utility Applications

A major potential use for the char lies in those areas normally served by the feed coal. In the case of the high-sulfur bituminous coals, the primary use has historically been fuel for thermal power generation. This market is currently met by processing the coal through minemouth preparation facilities to reduce its mineral sulfur and total ash content.

The most probable scenario for utility application of mild gasification char calls for the use of the finer coal fraction ($-1/4$ inch) from the coal preparation plant to feed a mild gasification facility. This material could be fed directly or, if desired, its ash content could be reduced by an advanced cleaning process. Previous work at Occidental Research Corporation laboratories⁵⁹ and the present investigations at UCC⁶⁰ have shown that the combustion characteristics of low-temperature carbonization char are similar to or better than those of coal.

The illustrative scenarios for the use of char in power generation are summarized in the following Figures I-64 and I-65, and discussed in the following paragraphs and in more detail in Appendix C.

Fine Char From Entrained-Bed Mild Gasification

Pulverized Fuel Boilers. Fine char from an entrained-bed mild gasification process would naturally integrate with direct hot feed to a pulverized coal-fired steam cycle. Its use for this purpose may be affected by its reduced volatile matter content, although hot feed would tend to lessen this effect. Alternatively, the hot fine char could be blended with moist feed coal and fed to the boiler through the conventional pulverizing mills and burners.

Slagging Combustion Turbines. Hot fine char could prove to be an advantageous feed for a dry-feed combustion turbine. The char could be transported to the turbine combustor feed lockhopper in carbonization gas. This eliminates the need for an inert gas to handle a fine preheated feed.

Entrained-Bed Integrated Gasification Combined Cycle. Hot, fine char could prove to be an efficient feed for a dry-feed entrained gasification system, such as the Shell Coal Gasification Process. The char feed could be transported to the gasification feed lockhopper in devolatilization gas. This eliminates the need for feed drying and preheating, and inert gas purging and blanketing normally required with a coal feed from atmospheric storage.

Figure I-64. USE OF ENTRAINED-BED CHAR FOR POWER GENERATION

Figure 1-65. USE OF FLUIDIZED-BED CHAR FOR POWER GENERATION

Magnetohydrodynamic (MHD) Generation. Hot fine char provides an efficient fuel for this advanced power generation system. The char could be preferred to coal because its lower hydrogen content improves the inherent MHD efficiency by reducing water formation during combustion.

Formed Fuels. The hot fine char can be consolidated into more easily handled forms by briquetting or pelletizing. These higher-density, low-dust solid forms are desirable for char storage or transport. The briquettes or pellets would also be suitable for blending with coal for shipment as a single fuel, where handling specifications would preclude direct blending of the fine char.

The formed char would also provide a suitable feed for moving-bed gasification in processes such as slagging or dry-bottom Lurgi. The reduced water and volatiles content of the char would eliminate problems with bed agglomeration and tar recovery. The uniform feed size would eliminate the need for coal fines separation from the feed.

Slurry Fuels. The fine char can also be slurried in water, oil, or perhaps methanol or CO₂ for economical pipeline transport. The low inherent water content of the char is an advantage in developing maximum slurry solids content for transport efficiency.

Coarse Char From Fluidized-Bed Mild Gasification

The hot char may be ground for use as described above. The coarse material is, however, directly suited for the following uses: circulated or bubbling fluidized-bed boilers, circulating or fluidized-bed gasification combined cycle, or coal blending.

Circulating or Bubbling Fluidized-Bed Boilers. The hot char product is of a size consist directly suitable for use as feed to a fluidized-bed or circulating-bed boiler for steam cycle power generation.

Circulating or Fluidized-Bed Gasification Combined Cycle. The hot char is suitable for direct-feed coarse-solids-feed gasification processes. As a result of its being partially devolatilized, it will not have a tendency to agglomerate, and this can simplify the design of the gasifier. Transport of the hot char feed in devolatilization gas will also eliminate lockhopper venting and purging as needed for coal feed from atmospheric storage.

Coal Blending. The coarse char from mild gasification will have a similar size consist as the fraction withdrawn from the coal preparation plant to feed the mild gasification step. For this reason, the hot product char can be directly blended with the balance of the treated coal from the preparation plant with potentially beneficial impact on overall product size consist and moisture content. The other effect will be a reduction in volatile matter and an increase in ash content.

Nonutility Applications

In addition to the above potential uses for char, which are directed at the production of electrical power, the char may find other uses that have historically been filled by coal- or petroleum-derived carbonaceous solids. Identified potential uses are described below.

As in the above uses described for power generation, the most probable source of char will be a mild gasification facility sited at a coal preparation plant. The feedstock would normally be the finer fraction of the size consist, which may be used directly or subjected to a coal cleaning step for enhanced rejection of mineral matter.

Illustrative nonutility applications for the char produced are shown in the following Figures I-66 and I-67, and are discussed in the following paragraphs.

Fine Char From Entrained-Bed Mild Gasification

Pulverized Fuel Use. Efficient use of the hot char as withdrawn from the mild gasification step would require the char production facility to be sited adjacent to the user. This may be a suitable approach for large users such as iron production or processing facilities, cement manufacturing facilities, lime manufacturing, or other large-scale users of heat that can be provided by a pulverized char fuel.

Entrained-Bed Char Gasification. The hot, fine char from the mild gasification could provide an efficient feedstock for entrained-bed gasification processes, such as the Shell Coal Gasification process. The gas product could then be used all or in part for such uses as hydrogen generation or synthesis gas production. Some hydrogen might be consumed in hydrotreating portions of the liquid co-product. Synthesis gas could find application for production of methanol or other chemicals.

Figure I-66. NONUTILITY APPLICATIONS FOR CHAR FROM
ENTRAINED BED MILD GASIFICATION

A88010026P

Figure I-67. NONUTILITY APPLICATIONS FOR CHAR FROM FLUIDIZED BED MILD GASIFICATION

Formed Char Products. The fine char can be made more manageable for transporting to remote users by forming it into uniform briquettes or pellets. In this form, the char may be suitable for export to foreign markets where this type of fuel is commonly used to meet both domestic and industrial fuel requirements.

Metallurgical Uses. The char briquettes or pellets may be further sintered and devolatilized to yield a "form coke" useful for metallurgical processes, such as blast furnace production of iron or foundry, ore roasting, and reduction processes.

Moving-Bed Gasification. The char in briquette form may provide an efficient feedstock for gasification in a moving-bed process, such as the British Gas/Lurgi slagging gasifier.

Blends for Processing. The partially devolatilized char may be used in blends with coal for use as feed to coking processes, production of graphite, and possibly for carbon electrodes. The blending of rapidly heated low-temperature carbonization char with coal has been observed to significantly improve the physical properties of the resulting metallurgical coke.⁶¹

Activated Carbon. The hot, fine char that has been partially devolatilized can be increased in surface area and pore volume by a controlled reaction with steam. Such an integration with the mild gasification may permit the production of a low-cost activated carbon for such uses as water purification, waste treatment, air purification, and catalyst supports. A char sample produced during free-fall devolatilization of an Illinois No. 6 coal in He at 1200°F, as a part of a State of Illinois coal research program, was extracted with double-deionized water. The extract analyzed in the EP toxicity list of metals including silver, barium, arsenic, cadmium, chromium, mercury, lead, and selenium. It was determined that the concentration of these elements were all below detection limit. Hence it is concluded that by steam activation of mild gasification on char, it may be possible to produce adsorbent carbon or char with the desired pore volume, pore size distribution, and surface area.

Coarse Char From Fluidized-Bed Mild Gasification

In addition to the above uses for fine char, which can be supported by further size reduction of the coarse char, the coarser char size consists makes it immediately suitable for selected uses.

Circulating or Fluidized-Bed Gasification. The hot, dry, and already gas-blanketed char can provide an efficient feed to a fluidized-bed gasification process. Its temperature and noncaking properties are particularly advantageous in eliminating bed agglomeration and in reducing the oxygen requirement.

Activated Carbon. The fluidizable size consist of the char facilitates its steam activation in a fluidized bed and will yield a similar size consist of activated carbon.

Summary of Char Utilization Methods

Char from the mild gasification process has potential applications in both utility and nonutility end uses. The particular applications differ in some respects for fine (-200 mesh) char, as produced by entrained-bed mild gasification, and for coarse (up to 1/4-inch) char, as produced by fluidized-bed mild gasification.

Fine char could be employed as a direct feed for an onsite or across-the-fence utility using pulverized-coal boilers, slagging combustion turbines, entrained-bed gasification combined-cycle power generation, or magneto-hydrodynamic power generation. The char could also be combined with pulverized coal for feed to nearby pulverized-fuel boilers. For remote power generation, the fine char would require size adjustment by pelletizing or briquetting, or by hot blending with coal. The consolidated solid fuel could also be used as a feed to a moving-bed gasifier. Fine mild gasification char could also find use as a slurry fuel. In addition to the electric power utility applications, the fine char could be utilized as a pulverized fuel for other large industrial users or as a gasifier feedstock for hydrogen or synthesis gas production. Fine char can also be used as a blending stock to improve the properties of metallurgical coke produced from coking coals. In the form of pellets or briquettes, the char can be used as a domestic or industrial fuel, or can be further carbonized to yield a form coke suitable for metallurgical or chemical reduction purposes. By means of steam activation, the char porosity can be increased for use as an active carbon for air and water purification, or for catalyst support material.

Coarse char, which would be generated by a fluidized-bed mild gasification reactor, could be pulverized by conventional means and fed to a

pulverized-fuel boiler, used as a direct feed to a circulating or fluidized-bed boiler or gasifier, or blended hot with coal to yield a utility fuel product suitable for transport to remote points of use. As with fine char, the coarse char can be used to make fuel pellets or briquettes for eventual processing into domestic or industrial fuel or form coke. The size consist of the coarse char also facilitates its transformation into active carbon by steam activation.

The recommendations for char utilization are given later, following the discussion of the market survey results, as they are based on the supply versus demand of the value-added products.

Condensable Hydrocarbons Upgrading Methods

The properties of the condensable product from mild gasification will depend on many factors, including the type of coal processed, the temperature of the mild gasification step, the particle heating rate, the solid and gas residence times, and the composition of the gaseous medium. However, certain characteristics will be held in common regardless of the processing conditions, within the limits of mild gasification. The condensable liquids will consist of a heavy organic phase, classified as tar; an aqueous phase, denoted as liquor; and a volatile organic phase, which generally must be recovered from the noncondensable gases by scrubbing, classified as light oil. The characteristics of these condensable fractions are discussed below.

Properties of Condensable Hydrocarbons

Coal Tar

The heavy organic, or tar, portion will have certain key characteristics that will influence the approach to upgrading, among which are the following:

- Carbon-to-hydrogen (C/H) ratio
- Boiling point distribution
- Heteroatom (S, N, and O) content
- Viscosity
- Density
- Suspended solids content
- Tar acids and bases

- Solvent fractionation analysis (oil, asphaltene, and pre-asphaltene)
- Quinoline insolubles.

Tables I-15 and I-16 compare some of the characteristics of tars from various sources with typical petroleum crudes.⁶² It is apparent that, while the coal-derived condensables are enriched in hydrogen compared to coal, their C/H ratios are higher than that of crude oil. Figures I-68, I-69, and I-70 show how the sulfur, nitrogen, and oxygen contents of the devolatilization products from the COED process vary with the heteroatom content of the feed coal.⁶³ All of these heteroatoms are present at reduced levels in the coal devolatilization liquids, compared to the coal.

Table I-15. COMPARISON OF COED FEED COALS AND CONDENSABLES PRODUCED⁶²

	<u>Western Kentucky</u> <u>Feedstock</u>		<u>Pittsburgh Feedstock</u>	
	<u>Coal</u>	<u>Raw Pyrolysis Oil</u>	<u>Coal</u>	<u>Raw Pyrolysis Oil</u>
Ultimate Analysis (wt %, mf)				
Carbon	71.3	82.3	73.8	82.9
Hydrogen	4.9	7.5	5.3	7.3
Nitrogen	1.6	1.2	1.2	0.9
Sulfur	3.1	1.5	3.9	2.3
Oxygen	8.6	6.3	7.4	5.9
Ash	10.5	1.2	8.4	0.7
API Gravity of Oil at 15.6°C		-6.4		-7.4

Table I-16. COMPARISON OF AN INDIAN COAL LIQUID AND PETROLEUM CRUDE⁶²

<u>Properties</u>	<u>Coal Syncrude</u>	<u>Nahorkatiya Crude</u>
Analysis (wt %)		
Carbon	85.8	86.7
Hydrogen	9.7	12.5
Sulfur	0.67	0.27
Nitrogen	0.71	0.05
Ash	0.012	0.015
C/H wt Ratio	8.8	6.9
API Specific Gravity at 15.6°C/15.5°C	9.5	29.5
Viscosity at 38°C (cSt)	60.95	5.8

Figure I-68. SULFUR CONTENTS OF COAL AND COED OIL⁶³

Figure I-69. NITROGEN CONTENTS OF COAL AND COED OIL⁶³

Figure I-70. OXYGEN CONTENTS OF COAL AND COED OIL⁶³

More detailed chemical characterization of the coal tar reveals the wide range of chemical compound types that are present, and the variation in the distribution of these products with the type of devolatilization conditions that have been used. In a treatise on coal tar,¹³ McNeil reviewed the compositions of coal tars from coke ovens (>1840°F), continuous vertical retorts (~1500°F), Coalite retorts (~1200°F), and Lurgi gasifiers. A comparison of these tars is shown in Table I-17. An examination of the average United Kingdom data shows that the coke-oven tars have a higher content of light oils, aromatics, and pitch, but lower phenols, cresols, and xylenols (PCX) and tar bases compared to the low-temperature tar from the Coalite process. This is consistent with trends identified and discussed earlier, under Subtask 1.1.

It has been determined, in a DOE-sponsored study at the Massachusetts Institute of Technology (MIT),⁶⁴ that the presence of a sulfur sorbent, calcium oxide, in coal gasification tends to promote the removal of phenolic oxygen, reduce the mutagenicity, and increase the H/C ratio of the condensables. Tar components in the molecular weight range of 350 to 600 were found to be preferentially affected by cracking reactions.

Table I-17. TYPICAL DISTILLATION CUTS FROM COKE-OVEN, CONTINUOUS VERTICAL RETORT, AND LOW-TEMPERATURE RETORT TARS¹³

Coke-Oven Tar		CVR Tar		LTC Tar	
Product Cut	Range, °F	Product Cut	Range, °F	Product Cut	Range, °F
Light Oil	≤360	Light Oil	195-340	Light Oil	≤360
Carbolic Oil	360-400	Carbolic Oil	360-460	Middle Oil	360-590
Naphthalene Oil	390-450	Light Creosote Oil	450-570	Wax Oil*	570-750
Wash Oil	465-555	Heavy Creosote Oil	525-680	Medium-Soft Pitch	Residue
Heavy Anthracene Oil	≤570	Medium-Soft Pitch	Residue		
Medium-Soft Pitch	Residue				

* Solidifies at 68°F (20°C) because of high paraffin was content.

Light Oil

The light oil portion, actually a mixture of volatile hydrocarbons that are scrubbed from the gas after condensation of the tar and liquor, consist principally of BTX and other low-boiling organic materials, which are also found to some extent in the tar fraction.

Liquor

The aqueous, or liquor, portion of the condensables will contain most of the ammonia, dissolved gases (CO_2 , H_2S , etc.), and a relatively small fraction of the organic liquids, which are primarily water-soluble phenols.

Conventional Upgrading Technologies in Coal Carbonization

Coal carbonization has been practiced for metallurgical coke production for more than 300 years, although recovery of liquid by-products did not become an important consideration until the last century, when many uses for tar chemicals began to emerge. The wide variety of by-products and chemicals that could be produced is dramatically illustrated by the coal by-product tree in Figure I-71. The development of the by-product coke oven led to the utilization of coal tar for the recovery of many substances that are now made primarily from petroleum products. The technology for the recovery and processing of coal tar, liquor, and light oils is well-established, although the volume of such materials processed has declined greatly since the end of the Second World War.

Perch⁶⁵ has reviewed the recovery of chemical products from coke ovens. Figure I-72 shows a flow diagram of a typical direct by-product recovery plant.²⁰ In the conventional tar processing plant attached to the coke-making facility, the tar-, liquor-, and oil-laden coke-oven gas is subjected to spray quenching with a flushing liquor derived from the condensate, consisting essentially of a solution of ammonia salts. The gas stream is cooled in two or more stages to about 68° to 86°F (20° to 30°C), resulting in the condensation of most of the tar and liquor. These phases are separated in a decanter.

In some plants, ammonia is recovered by treating the liquor with an excess of sulfuric acid, which results in the liquor becoming saturated in ammonium sulfate from ammonia in the gas. The ammonium sulfate is then recovered from the saturator device in the form of solid crystals. In other

Figure I-72. SCHEMATIC DRAWING OF A TYPICAL COKE-OVEN BY-PRODUCT RECOVERY SYSTEM

designs, ammonia is distilled from the liquor and incinerated; the economics of the recovery scheme will dictate which approach is to be used.

Part of the naphthalene in the gas stream, if present in sufficient quantities, is condensed in the final cooling stage and can be skimmed off or extracted from the aqueous phase. The aqueous phase is recycled to the system for further ammonia recovery. The balance of the naphthalene produced remains with the tar fraction, from which it is recovered during tar fractionation.

The cool (70°F) liquor from the final cooler is generally treated with lime or caustic to release free ammonia, which is then steam-stripped and recycled to the saturator or the incinerator, depending on the option chosen.

The cooled gas exiting the coolers will be saturated with light oil vapors; the method used to remove these is oil scrubbing, using either a petroleum-derived oil or a distillation cut from the middle fraction of the coal tar as a wash oil. The light oil, sometimes termed "benzol," can then be steam-stripped from the higher-boiling wash oil. The recovered light oil, primarily BTX, can be sold as is or further refined to remove sulfur-containing components by acid-washing or hydrotreating.

The recovered tar is fractionated by distillation to produce a number of cuts, depending on the composition of the tar and the end uses desired. Table I-17 showed the typical distillation cuts from coke-oven tar, continuous-vertical-retort (CVR) tar, and low-temperature carbonization (LTC) tar.¹³ These patterns are flexible to some degree.

In most continuous tar stills, the tar is filtered, dehydrated by heat exchange, heated under pressure to ~680°F, then flashed to separate the oil fractions from the pitch residue. Alkali is usually added prior to dehydration to inhibit corrosion caused by tar acids (phenols). Figure I-73 shows the design of a typical atmospheric tar-distillation plant.⁶⁶ In some cases, vacuum distillation is used.

Light oils contain benzene, toluene, and xylenes (BTX) or crude benzene ($\leq 300^\circ\text{F}$), naphtha (300° to 375°F), and a creosote residue. The naphtha cut also contains indene, which is valuable as a source of polyindene resins. Pyridine bases and phenols, cresols, xylenols (PCX) also comprise part of the naphtha fraction.

Figure I-73. SCHEMATIC DRAWING OF A TYPICAL COAL TAR DISTILLATION PLANT
(Teerverwertung-Koppers)

The middle cuts (carbolic oils, naphthalene oils, etc.) from the tar distillation contain the bulk of the tar acids (PCX) and bases. Phenols can be recovered by treatment with aqueous sodium hydroxide (caustic soda), resulting in an aqueous solution of phenols called "cresylate." The phenols can then be released, or "sprung" from the cresylate by reaction with CO_2 . Tar bases, including pyridines, lutidines, and picolines, can then be recovered from the remaining tar by washing with sulfuric acid, followed by neutralization with alkali and distillation of the basic oils.

Naphthalene, which is used for phthalic anhydride production, is also recoverable from the middle oils. This is in addition to the naphthalene that is condensed from the cooled devolatilization gases in the final spray-cooler. The concentration of naphthalene in low-temperature tars, however, is generally low, as shown in Table I-18.

Higher-boiling fractions from the middle oil, and the heavy oil fraction, are used primarily as feedstocks for creosote oil blends. Part of the middle oil fractions can also be used as a wash oil for light oil scrubbing, as described earlier. In some countries, anthracene oil is still recovered for the manufacture of anthraquinone and dyestuffs, but this is no longer practiced in the United States.

The coal tar distillation residue, or pitch, is a black glassy solid at room temperature that softens gradually over a broad temperature range. The characteristics of the pitch vary widely, depending on the source of the coal tar from which it is derived. The crude pitch is often treated further by simple heating or by air oxidation to improve its properties for various end uses, such as binder for electrodes used in aluminum manufacture.

In addition to chemicals recovered from the tar, there is a small quantity of organic material remaining in the liquor following ammonia removal. These are primarily phenols, including dihydric phenols such as resorcinol and catechol. These substances must be removed prior to the disposal of the waste liquor, either by solvent extraction or by bacterial oxidation. If solvent extraction is used, the phenols can be regenerated by treatment of the solvent with aqueous alkali.

Table I-18. CONSTITUENTS OF COAL TAR FROM VARIOUS SOURCES⁶⁵

Component, wt % of Dry Tar	Coke-Oven Tars				US Av	CVR Tars, UK		Low- Temperature Tars, UK Av
	United Kingdom		FRG Av	Av		Range		
	Av	Range						
Benzene	0.25	0.12-0.42	0.4	0.12	0.22	0.14-0.26	0.01	
Toluene	0.22	0.09-0.35	0.3	0.25	0.22	0.17-0.29	0.12	
o-Xylene	0.04	0.02-0.07		0.04	0.06	0.05-0.08	0.05	
m-Xylene	0.11	0.08-0.18	0.2	0.07	0.13	0.11-0.18	0.10	
p-Xylene	0.04	0.02-0.07		0.03	0.05	0.04-0.07	0.04	
Ethylbenzene	0.02	0.01-0.05		0.02	0.03	0.02-0.04	0.02	
Styrene	0.04	0.02-0.04		0.02	0.04	0.02-0.06	0.01	
Phenol	0.57	0.14-1.15	0.5	0.61	0.99	0.49-1.36	1.44	
o-Cresol	0.32	0.10-0.34	0.2	0.25	1.33	0.77-1.53	1.48	
m-Cresol	0.45	0.16-1.0	0.4	0.45	1.01	0.58-1.33	0.98	
p-Cresol	0.27	0.07-0.70	0.2	0.27	0.86	0.50-1.03	0.87	
Xylenols	0.48	0.13-1.30		0.36	3.08	2.70-3.58	6.36	
High Boiling Tar Acids	0.91	0.31-2.09		0.83	8.09	6.57-11.1	12.89	
Naphtha	1.18	0.52-2.66		0.97	3.21	2.86-3.84	3.63	
Naphthalene	8.94	7.29-11.31	10.0	8.80	3.18	2.15-3.84	0.65	
a-Methylnaphthalene	0.72	0.60-0.86	0.5	0.65	0.54	0.46-0.64	0.23	
b-Methylnaphthalene	1.32	1.15-1.63	1.5	1.23	0.68	0.62-0.74	0.19	
Acenaphthene	0.96	0.42-1.28	0.3	1.05	0.66	0.50-0.80	0.19	
Fluorene	0.88	0.46-1.80	2.0	0.64	0.51	0.33-1.23	0.13	
Diphenylene Oxide	1.50	1.40-2.00	1.4		0.68	0.62-0.74	0.19	
Anthracene	1.00	0.52-1.38	1.8	0.75	0.26	0.18-0.30	0.06	
Phenanthrene	6.30	2.30-9.80	5.7	2.66	1.75	0.40-2.90	1.60	
Carbazole	1.33	0.58-1.73	1.5	0.60	0.89	0.14-1.43	1.29	
Tar Bases	1.77	1.25-2.60	0.73	2.08	2.09	1.81-2.47	2.09	
Medium Soft Pitch	59.8	49.5-63.9	54.4	63.5	43.7	41.0-49.3	26.0	

Conventional Upgrading Technologies in Coal Liquefaction and Petroleum Refining

Coal liquefaction processes have been developed to produce substitute liquid fuels. For this end use, it is necessary to alter the characteristics of the liquid product by increasing the H/C atomic ratio and by reducing the heteroatom content. The methods by which coal tar can be upgraded in a similar manner is based on conventional practice in the petroleum refining industry:⁶⁷

- Hydrotreating
- Hydrocracking
- Catalytic cracking
- Steam cracking
- Reforming.

Crynes⁶² reviewed the status of the treatment of coal liquids by these methods in 1981. The following paragraphs include information based on that review.

Hydrotreating

Also termed "hydrofining," this is the treatment of a liquid feedstock with hydrogen under conditions favoring significant heteroatom removal, but only limited hydrogen addition. Generally a separate treatment prior to more extensive hydrogenation, the method uses metal oxide catalysts, usually cobalt and molybdenum oxides on alumina, nickel oxide, nickel thiomolybdate, tungsten and nickel sulfides, or vanadium oxide. Investigators at CSIRO have reported significant improvements in condensables properties following hydrotreatment using sulfided steelwool as a catalyst.⁶⁸

For coal-derived liquids, conditions for hydrotreatment are generally in the temperature range of 570° to 800°F, at pressures between 1500 and 2500 psig. It has proven especially difficult to remove nitrogen from coal liquids by hydrotreatment. Condensable products from the COED pilot plant have been extensively studied for upgrading to syncrude or gas turbine fuel.

Figure I-74 shows distillation curves of the feedstock and product oils from hydrotreatment with a nickel oxide-molybdenum catalyst on alumina at 720°F and 3000-psig pressure. The problem of catalyst deactivation has been

Figure I-74. DISTILLATION CURVES FOR FEED AND PRODUCTS OF COED OIL⁶²

noted to be significant with coal-derived liquids, which typically contain finely divided high-ash char particles. It has also been noted in several studies that the distribution of heteroatoms among the different boiling-range oil fractions influences the success of heteroatom removal, with the lighter fractions proving more susceptible to removal of sulfur, nitrogen, and oxygen.

Investigations at IGT with shale-derived oils have shown that, using a commercial Ni/Mo (Cyanamid HDS-9A) catalyst, over 50% of the nitrogen content could be removed by hydrotreating at 750°F and 2000 psig. This was increased to 80% by acid-washing the hydrotreated oils. Nearly complete sulfur removal was achieved during the hydrotreatment step.⁶⁹

Hydrocracking

Hydrocracking refers to hydrogenation of the feedstock in the presence of a catalyst, accompanied by extensive heteroatom removal and reduction of the molecular weight of the feedstock. The usual catalysts include platinum on a silica/alumina base and zinc chloride.

Coal liquids are more difficult to hydrocrack than petroleum feedstocks, again because of the high heteroatom content, but also because of the high level of polynuclear aromatics. Catalysts with high porosity and large pore diameters are desirable to maintain catalyst activity under conditions of the buildup of solid contaminants. The hydrogen consumption in hydrocracking is typically about double for coal liquids compared to petroleum-derived liquids.

Studies of hydrocracking extracts from the Consol CSF process have been conducted in batch and continuous reactors. Table I-19 compares the results of hydrotreatment (Co-Mo-Ni catalyst) and hydrocracking (ZnCl_2) of a coal oil from Consol's CSF process.

Hydrocracking results in a higher conversion of +750°F (+400°C) material, lower gas make, and a much higher yield of distillate oils (C_5 -392°C). However, there are several problems associated with the use of halide catalysts, including accumulation of ammonium salts in the catalyst, the large amount of catalyst required, and the potential of corrosion in the presence of water.

In a study by Utah Power and Light for EPRI, tar from the carbonization of Utah high-volatile bituminous coal in a Lurgi-Ruhrgas reactor was subjected to hydrocracking³⁶ to produce low-boiling distillates. The Lurgi tar, similar in nature to rapid-pyrolysis tars from entrainment reactors, underwent about

Table I-19. COMPARISON OF RESULTS OF HYDROTREATING WITH
HYDROCRACKING OF A COAL-DERIVED LIQUID⁶²

<u>Composition of Feedstock, wt %</u>	<u>+400°C Residue</u>
Hydrogen	6.82
Carbon	90.79
Nitrogen	1.17
Oxygen	1.07
Sulfur	0.15
Benzene Insolubles	3
Asphaltenes	30
Oil	67

Catalyst Data

<u>Property</u>	<u>Co-Mo-Ni (0.1, 6.8, 3.8%) on Silica-Alumina</u>	<u>ZnCl₂ Melt</u>
Pressure, psig	4200	4200
Temperature, °C	441	427
Time, min	60	60
Catalyst/feed, wt ratio	0.3	1.00
Conversion, wt % feed	29.6	77.6
(C ₁ -C ₃)100/Conversion	13.4	9.5
Distillates		
(C ₅ -150°C)	7.0	52.5
(150°-200°C)	1.7	10.4
(200°-400°C)	16.9	6.3
MEK-Soluble + 400°C Residue	67.5	19.0
Hydrogen Consumption, wt % feed	2.64	6.82

30% conversion of +932°F (+500°C) material to distillate oil. Problems associated with contamination of the condensables with carry-over char impeded efforts to produce distillate fuels.

Catalytic Cracking

The cracking of liquid feedstock in the presence of catalyst, without hydrogen, is termed catalytic cracking. In the petrochemical industry, this is done to reduce the molecular weight of heavy oil fractions. Catalysts

typically used include rare earths, nickel, vanadium, and/or iron on an alumina support.

Studies on COED oils have shown that coal liquids are more susceptible to coke and gas formation than are petroleum stocks treated by this method. Table I-20 shows the results of catalytic cracking of a coal oil using two different catalysts.⁷⁰ More than half of the oxygen in the feed oil was reportedly removed.

Table I-20. CATALYTIC CRACKING OF A COAL OIL⁷⁰

Properties	Catalyst		
	Silica-Alumina	Filtrol	Filtrol
Temperature, °F	860	860	950
Liquid Product Yield, wt %	86.0	69.2	62.3
Naphtha, wt %			
In Feed	11.2	11.2	11.2
In Product	26.1	36.0	40.8
Total Yield	22.4	24.9	29.9
Net Yield	11.2	13.7	18.7

Steam Cracking

Catalytic cracking conducted in the presence of steam is called steam cracking. This method is used to crack petroleum naphtha fractions to ethylene and other petrochemicals.

Investigations with coal liquids indicate that pre-hydrotreatment would be necessary to achieve satisfactory yields from steam pyrolysis. A comparison of steam cracking of a hydrogenated Synthoil liquid, a light petroleum feedstock, and decahydronaphthalene, revealed that the coal liquid and the hydroaromatic compound both produced less ethylene, but more benzene, than the petroleum-based material. These results are shown in Table I-21.

Reforming

Reforming is the processing of low-octane petroleum fractions in the presence of specific catalysts (molybdenum, platinum) to increase the octane number of the feedstock. This is done by promoting the aromatization of paraffins and cycloparaffins and the isomerization of straight-chain to branched-chain paraffins. The metallic catalysts (platinum/alumina) used are sensitive to poisoning from heteroatoms, and thus pretreatment of the feedstock is necessary before reforming can be accomplished.

Table I-21. STEAM CRACKING OF VARIOUS HYDROCARBON LIQUIDS⁶²

	Feedstock Sample		
	Hydrogenated Coal Liquid	Light Gas Oil Petroleum Distillate	Decahydro- naphthalene
Specific Gravity at 15°C/15°C	0.895	0.828	0.883
Hydrogen, wt %	12.76	13.70	13.12
Carbon, wt %	87.14	86.16	86.88
Hydrocarbon Group Types, wt %			
n-Paraffins	0.0	23.50	0.0
i-Paraffins	1.0	33.40	0.0
Alicyclics	83.1	23.00	100.0
Aromatics	12.8	20.10	0.0
	<u>Distillation</u>	<u>Temperature, °C</u>	
Fraction, vol %			
0 (IBP)	184	193	187
10	245	238	
30	268	271	
50	285	293	191
70	304	318	
90	333	351	
100 (EP)	348	389	196
Product Yields, wt %			
Hydrogen	1.03	0.60	1.05
Methane	11.66	12.00	10.35
Acetylene	0.49	0.39	0.54
Ethylene	18.83	22.66	19.36
Ethane	2.40	3.96	2.86
Propadiene, Propyne	0.58	0.41	0.29
Propylene	7.83	13.02	6.57
Propane	0.21	0.34	0.20
1,3-Butadiene	4.68	4.82	4.65
Butenes	1.63	3.12	1.41
C ₅ Olefins, Diolefins	2.56	2.72	2.24
Benzene	12.15	6.71	17.97
Toluene	6.76	3.51	10.34
C ₈ Aromatics	3.43	2.11	4.88
Other C ₆ -C ₅	0.48	0.50	0.42
C ₉ + to 205°C	2.82	2.61	5.21
Pyrolysis Fuel Oil (-205°C)	22.46	20.51	11.66
Total	100.00	100.00	100.00

20WP/61089T2-10/RPP

Comparative tests of prehydrogenated COED-derived naphtha and petroleum naphtha indicate that the catalyst aging is actually slower with the coal liquid. The high aromatic content of the coal-derived liquid is advantageous to the attainment of high octane numbers, but sulfur and nitrogen contents must be reduced to 12 ppm by pretreatment.

Other Upgrading Methods

In a continuing DOE-sponsored study conducted at Oak Ridge National Laboratory,⁷¹ the upgrading of coal devolatilization condensables by solvent extraction and solid phase adsorption methods is being examined. Possible solvents and solvent blends identified as potential candidates as extraction media include formic acid, sulfur dioxide/benzene, phenol, furfural, and a blend of propane, cresol, and phenol. Solid sorbents considered in this program include attapulgite clays saturated with selected metal salts. Initial experiments on the extraction of UCC mild gasification condensables with 25% (v/v) aqueous formic acid have resulted in 10% removal of nitrogen and 41% removal of oxygen.

Summary of Condensable Hydrocarbons Upgrading Methods

Condensable hydrocarbons from mild gasification, consisting of tar, light oils, and liquor, can be upgraded by methods used in coal carbonization (phase separation, fractional distillation, and chemical treatment), by methods used in the petroleum refining and coal liquefaction industries (hydrotreatment, hydrocracking, catalytic cracking, steam cracking, and reforming), or by other methods (solvent extraction, solid adsorption). In all likelihood, a complete condensable upgrading scheme might employ some combination of methods from all three of these categories, depending on the degree of refining desired. The presence of a sulfur absorption additive in the mild gasification reactor can significantly impact the nature of the condensables by reducing heteroatom levels and promoting cracking of high molecular-weight components, but also may substantially reduce the condensables yield.

In coal carbonization, the tar is fractionated to yield the following: a portion of the light oil containing BTX, indene, and naphtha; a middle oil that contains the bulk of the phenols, cresylic acids, naphthalene, pyridine bases, and creosote oils; a heavy oil, which is mostly a creosote blending stock; and a pitch that may be further treated by heating or partial oxidation

to improve its properties for selected end uses. Low-temperature carbonization tars will typically contain more phenols, less naphthalene, and less pitch when compared to high-temperature coke-oven tars. In addition to the light oils recovered from the tar, most of the light oils are scrubbed from the fuel gas after it is cooled to room temperature. The aqueous liquor is separated for removal or recovery of ammonia, phenols, and other by-products prior to disposal and/or recycle.

Hydrotreating and hydrocracking methods have proven technically feasible for upgrading coal devolatilization condensables to levels of quality suitable for use as substitute liquids fuels, although the conditions necessary for adequate removal of heteroatoms and an increase in the H/C ratio have been generally found to be more severe than for petroleum-derived liquids. The high nitrogen and mineral matter contents of the coal-derived condensables have presented difficult challenges to the success of catalytic upgrading methods. Catalytic cracking, steam cracking, and reforming processes have been found to be useful in upgrading coal condensables that have undergone prior treatment by hydrotreating and/or hydrocracking.

Treatment of condensables by solvent extraction and solid-phase adsorption to reduce the heteroatom levels, while showing some promise, are still in the early stages of development.

Condensables Utilization Methods

The condensable product from the mild gasification process consists of a complex mixture of organic compounds, primarily aromatic, ranging in boiling points from benzene (b.p. 178°F) to polynuclear compounds boiling above 1000°F. The total product can be viewed primarily as a source of fuel or a source of chemicals and other products. The preferred options for utilization is determined by the market assessment of the value-added benefits.

Fuel Applications

The conversion of coal-derived condensables to substitute liquid fuels has been the subject of much study. As previously discussed, extensive upgrading is necessary, probably by the addition of hydrogen and the removal of heteroatoms from the raw coal-derived product. The resulting distillates have been evaluated for use as gasoline and diesel blending stocks, and also as high-density jet fuels. Figure I-75 shows a refining scheme proposed for evaluation by ARCO for a blend of hydrotreated COED oils.⁷²

Figure I-75. SCHEMATIC DRAWING OF ARCO PROGRAM FOR UPGRADING COED LIQUIDS⁷²

Gasoline

The principal gasoline-boiling-range (180° to 390°F) components of the condensables available from mild gasification are BTX. The entire BTX fraction may be suitable as an octane enhancer, although toluene and xylenes have traditionally been used for that purpose. There may also be substantial aliphatic content in the low-temperature tars from mild gasification, although the rapid-heating methods would tend to reduce the yield of paraffins. In general, the hydrotreated gasoline-range fraction from mild gasification can be viewed as an octane booster.

Diesel Fuel

The diesel-fuel boiling-range liquids (185° to 761°F) from the pyrolysis of Kentucky No. 9 coal and a cleaned coal from UCC were tested by Oak Ridge National Laboratory investigators.⁷³ Table I-22 shows how these oils compared with distillates from SRC-II, EDS, a shale oil fraction, standard No. 2 diesel fuel, and a Middle East crude oil light fraction. Performance of the fuel in test engines, when blended 20% with diesel fuel, was found to be very similar to performance with 100% diesel fuel. The yield of this fraction from coal was reportedly between 6.3 and 11.9 wt % maf coal.

Although the coal-derived diesel fraction performed satisfactorily as a blending stock, its chemical characteristics differed significantly from No. 2 diesel fuel, as shown in Table I-22. The sulfur and nitrogen levels in the diesel fractions produced from the UCC cleaned coal were 4.73 and 45.0 times higher, respectively, than in the No. 2 diesel fuel. Environmental considerations may require reduction of these heteroatoms before the coal-derived fuel can be used in engines outside of the laboratory.

Diesel fuel from Coalite liquids in the United Kingdom, amounting to about 22% of the raw tar, have been used in city buses in Bolsover.

Fuel Oil

An oil fraction from the Coalite plant in Bolsover, United Kingdom, has also been used as a blend for industrial fuel oil. This fuel can be used in industrial boilers to raise steam. As with other coal-derived liquid fuels, however, the removal of sulfur and nitrogen would be necessary for the fuel to be environmentally acceptable.

Table I-22. CHARACTERISTICS OF COAL CONDENSABLES AND OTHER LIQUID FUELS⁷³

	Pyrolysis Oil	Pyrolysis Oil UCC	SRC II Middle Distillate	EDS Middle Distillate	Western Shale Oil Crude	No. 2 Diesel Fuel	Crude Oil Middle East Light
	Kentucky #9						
Specific Gravity	0.98	0.94	0.97-0.98	0.94	0.91-0.95	0.85	0.85
Boiling Range, °C	85-405	85-395	158-350	208-350	150->540	147-409	79-565
Viscosity, 38°C, cs	7.0	4.2	3.7	3.3	16-79	2.0-3.0	
H, wt %	10.0	10.6	8.6-9.0	10.7	11.5	12.7	13.0
C, wt %	81.4	83.7	85.5-87.0	88.6	84.1	86.5	85.0
S, wt %	1.9	0.71	0.27-0.31	0.01	0.6-0.7	0.15	1.6
N, wt %	0.48	0.45	0.83-1.0	0.08	1.3-2.0	0.01	0.04
O, wt %	6.2	4.5	3.9-4.5				
H/C Atom	1.47	1.52	1.19-1.23	1.45	1.62	1.76	1.84
Higher Heating Value, Btu/lb	16,490	17,170	17,100	18,600		19,900	
Aromatics, vol %	49	47	88	84	32-72	30-36	38
Cetane No.	Undetermined		16-22	23	Unknown	40-50	Unknown
Yield of Naphtha and Distillate	6.3-11.9 wt % maf coal		18-26 wt % maf coal	<26 wt % maf coal	3.0 wt % shale	60-70 % of crude	60-70 % of crude

High-Density Fuel

The possibility has been raised of converting coal-derived oil fractions to specialty fuels with the characteristic of high volumetric energy density. Low-temperature tars such as produced by mild gasification would have some of the required characteristics, being relatively rich in alkylnaphthalenes and hydroaromatic structures. These fuels would find applications as jet and rocket "superfuels", which would substantially extend the range of jet aircraft. Hydrogenation would be required to remove heteroatoms and to increase the proportion of hydroaromatic structures.

Nonfuel Applications

Prior to World War II, coal was the primary source of chemicals in the industrialized world. Many of the chemicals once produced by coal are still in great demand, but the principal source has shifted to petroleum feedstocks. Among the chemicals that have been produced in significant quantities from coal-derived condensables are --

- Phenols, cresols, and xylenols (PCX)
- Benzene, toluene, and xylenes (BTX)
- Naphthalene
- Creosote and creosote oils
- Pyridine bases
- Indene-coumarone resins
- Medium-soft pitch
- Hard pitch.

In a recent report for the State of Illinois Department of Energy and Natural Resources, uses for PCX, BTX, and naphthalene were reviewed.⁷⁴ Information on these and other products has also been taken from McNeil.¹³

Phenols, Cresols, and Xylenols (PCX)

The light phenols, or tar acids, which are recovered from coal tar fractions by alkali treatment and re-acidification of the alkali wash with CO_2 , are extensively used in the chemical processing industry. Phenol ($\text{C}_6\text{H}_5\text{OH}$) is used for the production of phenolic resins, and also as a

feedstock for the production of bisphenol A and caprolactam, important starting materials for the production of many polymers and engineering plastics. Table I-23 shows some of the polymers that can incorporate phenol into their manufacture directly or indirectly.

Table I-23. POLYMERS THAT USE PHENOLIC CHEMICALS IN THEIR MANUFACTURE

<u>Name of Polymer Type</u>	<u>Phenolic Species Used</u>	<u>Principal Use Area</u>
Phenol-Formaldehyde (Bakelite)	Phenol	Building Materials
Polycarbonate (Lexan)	Bisphenol A Hydroquinone Resorcinol Catechol	Engineering Plastic
Polyester (Dacron, PET)	Polyoxybenzoate Dihydroxy-biphenyl Resorcinol Hydroquinone	Fibers, Fiberglass
Polysulfone (Udel)	Bisphenol A	Engineering Plastic
Polyamides (Nylon, Kevlar, Nomex)	Phenol (for Caprolactam)	Fibers, Eng. Plastic

Cresols are also used in the manufacture of polymer feedstocks. Mixed cresols, xylenols, and higher cresylic acids are used for disinfectants. The individual cresol isomers, ortho-, meta-, and para-cresol, can be separated and sold as specialty chemical for such diverse uses as inks, perfumes, pharmaceuticals, solvents, preservatives, and dyes. Tricresyl phosphate is a widely used plasticizer made from o-cresol.

Mixed cresylic acids, comprised of higher boiling phenolic mixtures, are used in the manufacture of phosphate esters, resins, solvents, froth-flotation agents, and antioxidants.

Benzene, Toluene, and Xylenes (BTX)

BTX can be separated by distillation into its individual components, including benzene, toluene, xylene isomers, ethylbenzene, and other alkyl derivatives. Benzene is a feedstock for a wide variety of specialty chemicals, the most important being ethylbenzene, isopropyl benzene, cyclohexane, and aniline. Ethylbenzene is dehydrogenated to make styrene for

the manufacture of polystyrene. Isopropylbenzene is converted to cumene, which eventually is peroxidized to phenol and acetone. Cyclohexane is another feedstock for the production of caprolactam, along with adipic acid. Both of these materials are used in the manufacture of nylons. Aniline, which can also be made from phenol, is used in the production of rubber, dyes, and isocyanates for polyurethane production.

Toluene, aside from extensive use as an octane enhancer, is a feedstock for the production of TNT and other explosives, and for toluene diisocyanate (TDI) for polyurethane manufacture. It is also used extensively as an industrial solvent.

Xylenes, in the form of a mixed-isomer stream, finds wide use as a solvent. The ortho-isomer is used for the manufacture of phthalic anhydride, which is an important feedstock for polyester resins. Para-xylene is used to make terephthalic acid, which is also used for polyester production. The widely used plastic film, polyethylene terephthalate, is made from this feedstock.

Naphthalene

In addition to its traditional use as an insect repellent, naphthalene, finds use in the manufacture of plasticizers, dyestuffs, coatings, and tanning agents. In the United States, a significant amount of phthalic anhydride is still made from naphthalene, although this use has been largely replaced by o-xylene from petroleum sources. Phthalic anhydride, as mentioned earlier, is important for the manufacture of polyester resins. Koppers Co., one of the largest coal tar processors in the United States, has recently re-engineered their Cicero, Illinois, phthalic anhydride plant to replace o-xylene with naphthalene as the primary feedstock for phthalic anhydride production.

Creosote and Creosote Oils

Creosote oils are by far the most widely used timber preservatives. These are made by blending the various boiling-point fractions remaining from coal tar after the removal of light oils, tar acids, and tar bases. Coal-tar creosote, especially the heavier fractions, are also used for the production of carbon black. The other major use for creosote is as a flux for coal tar pitch and bitumen in the manufacture of road binders.

Pyridine Bases

Pyridine bases, including pyridine, picolines, and lutidines, are present in greater quantities in low-temperature tars than in coke-oven tars, which contain primarily quinolines as the nitrogen bases. The pyridine bases find outlets in the manufacture of pharmaceuticals and dyestuffs, although these chemicals today are chiefly made by the synthetic route.

Indene-Coumarone Resins

More correctly termed polyindene resins, these polymers are made from a narrow fraction of the light oil which is rich in indene and also contains some phenol. In the presence of a catalyst, the oil is polymerized to yield a resin that is used in coatings and adhesives.

Medium-Soft Pitch

The untreated "medium-soft" pitch, which is a major product of coal-tar distillation, finds many uses, depending to a great extent on the properties of the pitch. The pitches from low-, medium-, and high-temperature processes vary in the coking properties, quinoline-insolubles, aromaticity, and other properties which influence the physicochemical behavior of the pitch. Low-temperature carbonization produces pitch which is generally considered to be unacceptable for upgrading to electrode-binder pitch, although thermal cracking under carefully selected conditions may produce an acceptable binder pitch from low-temperature carbonization. However, the principal uses for medium-soft pitch are as road-tar binders and for roofing tar.

In the United States, most road surface materials are made from bitumen (asphalt), a by-product of petroleum refining, although it has been reported that improved properties can be obtained from mixing bitumen and coal-tar pitches. Coal-tar pitch displays better adhesion, better resistance to water and petroleum-based oils, and a "self-healing property" by means of cold flow. Coal-tar-containing road surfaces also display and maintain greater skid resistance than all-asphalt coatings. However, these advantages are offset by a greater tendency to become soft and tacky in hot weather and crack in cold weather. Blends of coal-tar pitch with asphalt results in the most favorable blend of properties, and for this reason such blends are widely used in European countries.

For flat and low-slope roofing, coal-tar pitches are superior to asphalt in most characteristics, including the above-mentioned properties. There has reportedly been an increase in interest in coal-tar built-up roofing in recent years.⁷⁵

Much work has been done to develop techniques for creating high-modulus carbon fibers from coal-tar pitch. Rand,⁴⁴ in a recent paper on the rheology of pitches, shows how the balance of primary and secondary quinoline-insolubles (QI) affect the production of a "mesophase," state which is desirable for fiber spinning. Low-temperature pitches, which contain little primary QI compared to coke-oven pitch, appear to be suitable for this purpose following heat-treatment to increase the secondary QI content.

Medium-Hard Pitch

The principal use for coal-tar pitch from coke production, following heat treatment to convert softer pitch to medium-hard grade, is as a binder for electrodes used in aluminum smelting. As previously mentioned, low-temperature pitches have not been found suitable for this purpose, but the U.S. Bureau of Mines, in a 1967 study, produced carbon electrodes entirely from a low-temperature lignite pitch which was upgraded by thermal cracking.⁷⁶ The cracked-pitch yield was 20% to 40% of the soft pitch when the cracker temperature was maintained at 1450°F. The electrodes were made by combining the resultant pitch with pitch coke, produced from the same feedstock, and carbonizing the mixture. Bituminous coals would be expected to produce a more suitable pitch, due to the lower proportion of heteroatomic bridge structures in the coal as compared to lignite.

A smaller market exists for hard pitches as a binder for graphitized electrodes, which are used in electric-arc steelmaking.

The heat-treatment of pitch also results in the production of pitch coke, which can be used as the "grist", or solid portion of the electrode. Pitch coke can also be used in the production of other formed graphite products, such as refractory carbon bricks.

Summary of Condensables Utilization Methods

The utilization potential of the upgraded condensables from mild gasification of coal can be categorized into fuel and nonfuel uses.

The light oil portion of the condensables are valuable as octane enhancers for gasoline, following removal of heteroatomic components by hydrotreating or chemical treatment. Similarly, diesel fuel blending stocks have been produced from mild gasification condensables and tested in engines, with encouraging results. However, the costs of upgrading the fuel to meet emissions and long-term stability standards may be excessive in view of presently low crude oil prices. Heavier tar fractions can also be upgraded to be used as an industrial fuel oil, with similar considerations. The potential for mild gasification products for conversion to high-density jet fuels may be considerable, due to the relatively high content of hydroaromatic and alkyl naphthalene structures.

Aside from potential use as substitute liquid fuel feedstocks, a wide variety of chemicals can be obtained from mild gasification condensables. These include phenols, cresols, xylenols, and cresylic acids, which are valuable as feedstocks for many widely used polymers, as well as for inks, pharmaceuticals, solvents, preservatives, plasticizers, disinfectants, and dyes. BTX components are also used as chemical feedstocks for production of plastics, dyes, explosives, and solvents. Naphthalene is a source of phthalic anhydride for polyester resins and fibers. Creosote oils are the major timber preservatives in use today, and are also used for the manufacture of high-quality carbon black and in road binders. Pyridine bases are used in the manufacture of pharmaceuticals and dyes. Indene, from the light oil fraction, is used to make resins for coatings and adhesives.

The pitch, or distillation residue from coal-tar fractionation, is used for road and roof tars. Blended with asphalt, medium-soft pitches from low-temperature carbonization are used to produce high-quality road surfaces. A potential also exists for the conversion of medium-soft pitch to high-modulus carbon fibers through selected heat-treatment procedures. The conversion of medium-soft pitch to harder grades of pitch by thermal treatment or partial oxidation can be done, and the resulting product can be used as a binder for carbon electrodes used in aluminum and steel manufacture. Pitch coke produced from the cracking of softer pitch grades is also useful as a filler for electrode manufacture or as a chemical reductant.

The recommendations for condensables utilization are given later in the report, following the discussion of the market survey results, as they are based on the supply versus demand of the value-added products.

Fuel Gas Upgrading Methods

Properties of Fuel Gas

The medium-Btu fuel gas from mild gasification consists of hydrogen, methane and other hydrocarbons, and carbon oxides. If flue gases are introduced, nitrogen will also be present. The major contaminants requiring removal, following recovery of condensables, are H_2S and NH_3 . Table I-24 shows a typical gas composition expected from mild gasification of a bituminous coal. The upgrading methods that can be applied to the fuel gases do not differ substantially from those used for gas products from other coal conversion or coal carbonization processes. The information in this section is mainly drawn from a review by Grosick and Kovacic.⁷⁷

Table I-24. TYPICAL GAS COMPOSITION FROM MILD GASIFICATION OF HIGH-VOLATILE BITUMINOUS COAL IN NITROGEN (1220°F, 1.4 s Residence Time)

<u>Component</u>	<u>Volume, %</u>
H_2	28.2
CO_2	7.8
CO	20.4
CH_4	26.4
C_2H_4	7.2
C_2H_6	4.2
$\text{C}_3\text{H}_6 + \text{C}_3\text{H}_8$	3.1
$\text{C}_4\text{H}_8 + \text{C}_4\text{H}_{10}$	0.4
H_2S	<u>2.3</u>
Total	100.0
Molecular Weight	19.6

Upgrading Technologies

Ammonia Removal and Recovery

As described in the section on upgrading of condensables, ammonia can be scrubbed from the gas by absorption in a saturated, acidic ammonium sulfate liquor. In the U.S. Steel Phosam process, ammonia is removed by contact with acidic ammonium phosphate. In many carbonization plants, ammonia is incinerated in preference to recovery, in order to avoid unfavorable economics

related to the cost of the acidic reactant. However, environmental considerations may affect this practice.

If a sulfur-capture additive such as lime or iron oxide is used in the mild gasification step, substantial ammonia decomposition may result, reducing the requirement for ammonia removal.

Sulfur Gas Removal and Recovery

About 10% to 21% CaO by weight of coal, added to mild gasification of Illinois No. 6 and Pittsburgh No. 8 coals, has been observed to reduce the H_2S in the product gas to very low levels.^{78,79} If a solid additive is used in the mild gasifier as a sulfur getter, the H_2S and COS contents of the fuel gas is expected to be very low. In cases where the sulfur compounds must be removed from the fuel gas, methods commonly practiced in the coal carbonization and petroleum industries can be used. These methods include 1) absorption/desorption processes in which H_2S and COS are concentrated for separate gas-phase partial oxidation to elemental sulfur (Claus technology), and 2) liquid-phase catalytic oxidation processes in which the absorbed gases are also partially oxidized to produce elemental sulfur.

Light Gas Separation

If the fuel gas is sufficiently concentrated, separation of light gases may be profitable. The available methods of accomplishing this include cryogenic separation, pressure-swing adsorption, and membrane separation. This approach may be considered where hydrogen concentration in the fuel gas is acceptably high to consider isolating it for resale or specific onsite end uses.

Synthesis Gas

The production of methanol synthesis gas from the fuel gas by adjustment of the H_2/CO_2 ratio and catalytic shifting is an option for fuel gas utilization. Several commercial shift catalysts are available.

Summary of Fuel Gas Upgrading Methods

Fuel gas upgrading methods applicable to mild gasification are similar to those used in the coal carbonization and coal gasification industries. Ammonia can be scrubbed from the gas, in conjunction with gas quenching and condensation, by spray-quenching with an acidic recycle liquor. The liquor

will contain an ammonium salt, such as ammonium sulfate or phosphate. Depending on economics, ammonia will be recovered as a salt by-product or distilled and incinerated. The use of a sulfur-capture additive in the mild gasification reactor may enhance ammonia decomposition, reducing the level of ammonia in the product gas, in addition to reducing the level of H_2S and COS in the fuel gas by two or more orders of magnitude. Further sulfur gas removal can be effected by conventional methods that allow sulfur to be reclaimed as elemental sulfur (H_2S), sulfuric acid, or ammonium sulfate. HCN is also removed by these methods.

Depending on the concentration of hydrogen in the fuel gas and the methods used to recover condensables, a fractionation of the fuel gas into components by cryogenic separation, pressure-swing adsorption, or membrane separation may be desirable. The adjustment of the CO/H_2 ratio by catalytic shifting to produce a synthesis gas for methanol production is an additional option.

Fuel Gas Utilization Methods

The fuel gas from a mild gasification plant is expected to be in the low- to medium-Btu range of heating values, due to the use of a flue gas mixture for fluidization, which dilutes the product gas with noncombustible species. The use of the fuel gas for onsite process heat and steam generation is the expected major end use. Excess fuel gas can be utilized in other integrated applications or sold to nearby industrial users. Other possible uses of the gas product components are discussed below.

Fuel Applications

Industrial Fuel Gas

The heating value of the fuel gases from externally heated mild gasification processes were shown in Figure I-62. These values ranged from about 390 to 1100 Btu/SCF, declining with temperature over the range of 850° to 1450°F. In a fluidized- or entrained-bed system, the fuel gas would be diluted by the fluidizing or entraining gas. When a flue gas is used, the fuel gas would be diluted with nitrogen, thus lowering the heating value. The low-pressure low- to medium-Btu gas resulting from the process, following necessary cleanup, can be used in industrial burners or boilers for onsite heat or steam generation, or sold to nearby industrial users.

Methanol Synthesis for Fuel

Methanol from synthesis gas can be used directly as a motor fuel, or can be converted into gasoline using the Mobil process. The synthesis gas can also be converted to motor fuels by Fischer-Tropsch synthesis. There has been a revival of interest in the use of oxygenated fuel blends as a means to control air quality. Methanol may have an important role in the future of transportation fuels.

Nonfuel Applications

Hydrogen

Hydrogen can be recovered by the methods outlined previously (Light Gas Separation) and utilized for ammonia synthesis, hydrogenation of condensable fractions recovered from the mild gasification, or sold as a chemical feedstock. The use of fuel gas combustion with air for direct contact pyrolysis heat input will dilute the fuel and may preclude economic recovery of hydrogen.

Synthesis for Chemicals

The technology of converting synthesis gas to a wide variety of fertilizer and hydrocarbon chemicals is very well known. Methanol from synthesis gas can have a variety of end uses. In addition to its use as a fuel, methanol is used as a solvent and a feedstock to produce formaldehyde, glycols, and many precursors for plastics and polymers.

Summary of Fuel Gas Utilization Methods

The primary end use of the fuel gas will most likely be for onsite energy generation to raise process steam or for process heating. Fuel gases from low-temperature carbonization processes generally range in heating value from 390 to 1100 Btu/SCF. If synthesis gas production is shown to be an economically viable option, methanol can be manufactured for use as a motor fuel or as a feedstock for gasoline production. Methanol is also a valuable chemical feedstock for solvents and plastics. Hydrogen, if separated from the fuel gas by one of the methods outlined above, can be used for ammonia synthesis, char gasification, or the hydrogenation of selected condensable fractions. Hydrogen can also be sold as a chemical feedstock.

Co-products Upgrading Methods for Selected End Uses

Char Uses

Combustion

The upgrading methods appropriate to allow marketing of the char for combustion uses will depend largely on the shipping requirements and requirements of the fuel to meet emission standards.

For use of the char in a char/coal blend, no upgrading of the char is anticipated, either for onsite use or for remote use as practiced for the particular coal. It is anticipated that the increase in the ash content of the char will be compensated for by its reduced moisture content. Hot char addition to the coal blend may also result in overall moisture reduction through partial drying of the coal.

Direct firing of the hot char without blending may require added grinding if the product char is derived from a fluidized bed or other processes delivering a large particle-size char. Char from entrained processes may be suitable for direct firing in such end uses as fired boilers or furnaces, as supplementary fuel for blast furnace iron production, or as primary or supplementary fuel for metallurgical or other consumers of pulverized fuel.

Metallurgical Uses

For this use, the low-density, relatively fine particle-size char will have to be consolidated into a higher-density, stronger physical form through such means as briquetting. Additional devolatilization of the briquettes may also be employed if required to improve strength and reduce volatile matter content.

For some uses the ash and sulfur contents of the char may be excessive. In this case the feed coal to mild gasification could be treated for reduction of ash and mineral sulfur and the product char treated by exposure to steam to reduce its organic sulfur content. In some instances the addition to the char of a sulfur capture agent such as lime may be acceptable.

Active Char

For this use, the char will require steam treatment to increase its surface area and adsorption activity. Depending on the end use, the char may also require that the coal be pretreated to reduce mineral content of the resulting char product.

Char Gasification

For use in an integrated system of gasification, the char would be fed hot directly to a gasification process that would accommodate the size consist of the char. In this instance, no upgrading would be required. For remote use, or use in a moving-bed type of gasifier requiring a consolidated feed, the char would be briquetted or pelletized.

Domestic Fuel Use

For use as a domestic solid fuel, the char would require forming and pretreatments similar to that for metallurgical use, except for a lesser requirement for additional devolatilization. The critical characteristics of the briquette will vary, depending on the local use regulations and customer perceptions of acceptability. These latter requirements may be met by the addition of inert materials such as clay to retain the shape of the briquette during combustion, or by the addition of lime or other agent to capture sulfur.

Condensable Hydrocarbons Uses

Regardless of the char end use option selected, the condensable products from the mild gasification of bituminous coal will be processed by conventional coal-tar recovery and fractionation methods. The degree of refining utilized will be dependent on the economics of the recovery of specific streams; it is anticipated that minimal refining will be the preferred approach. The condensables will yield six major product streams:

- Light oil, the condensable fraction distilled from tar and scrubbed from the gas stream, boiling below 360°F
- Middle oil, the tar fraction distilling in the temperature range of 360° to 590°F
- Heavy oil, the tar fraction distilling in the temperature range of 570° to 750°F
- Medium-soft pitch, the untreated distillation residue from primary fractionation of the tar
- Medium-hard pitch, the improved pitch product from thermal treatment of the medium-soft pitch at 1400° to 1500°F
- Pitch coke, the solid carbonized product from thermal treatment of medium-soft pitch.

Chemical Feedstocks

The light and middle oil fractions can be marketed to the chemical refining industry for further refining into valuable chemicals, including the following: benzene, toluene, xylenes, phenol, cresols, xylenols, cresylic acids, naphthalene, indene, and pyridine bases. All of these chemicals are used in many ways in the production of polymers, pharmaceuticals, and other industrial and consumer products.

Octane Enhancers

Based on the market conditions for fuel feedstocks, the light oil fraction can be minimally refined to remove sulfur and yield a BTX mixture suitable as a gasoline octane enhancer.

Preservatives

The remainder of the heavy and middle oil fractions consist of creosote oil, which is used as a blending feedstock for timber preservative creosote. If refining of the middle oil to recover phenols, tar bases, and other chemicals is shown to be economically profitable, the remaining middle oil fraction can be sold for this purpose. The heavy oil fraction may also be salable as a creosote blend.

Binders

The medium-soft pitch produced from distillation of low-temperature tars are suitable for road and roof binders. Although most road-building in the United States is done with petroleum-based asphalt, the specifications for road materials in at least some states are written specifically for coal-derived binders. As previously discussed, blends of asphalt and coal-tar pitch yield the most desirable blend of properties. The same general statements can also be made for binders for flat or slightly pitched roofing. The mild gasification process scheme can offer the option to process all of the pitch to hard pitch or to market the medium-soft pitch directly for these purposes, depending on market considerations.

Although the medium-soft pitch is suitable as a road and roof binder, it does not have the properties required for electrode binder pitch without further upgrading. Improvements in coking value and rheological properties may be attained by thermal cracking at 1400° to 1500°F. The medium-hard pitch

produced in this way is suitable for sale as a binder in the manufacture of carbon electrodes for the aluminum and steel industries.

Fillers

Carbon black is a filler and pigment in rubber products, chiefly automobile tires, and in chemical coatings. As described, creosote oil fractions can be used for carbon black production. The heavy oil is preferred for this purpose, and most heavy coal-tar oils that cannot be used for creosote blending find an outlet in carbon black production.

The pitch coke made as a by-product of pitch cracking can be sold as a "grist", or filler, used in the manufacture of carbon electrodes. The material has been found to be acceptable as a substitute for petroleum coke in this and other uses, such as alkaline chloride electrolysis. It is possible that low-temperature pitch, due to the lower content of primary quinoline in solubles, would produce pitch coke with superior graphitizing properties, when compared to coke-oven pitch.⁸⁰

Fuel Gas Uses

Onsite Combustion

Following gas cleaning to satisfy emission standards, the bulk of the fuel gas produced by mild gasification will be used to provide energy for the mild gasification reactor through the generation of hot flue gases for fluidization/entrainment of the incoming coal. Part of the fuel gas may also be recycled to the mild gasifier without burning, depending on the heat demand of the coal feed and the desired composition of the fluidizing gas. The fuel gas can also be burned to provide heat for low-pressure steam generation, coal drying and preheating, fractional distillation of the condensables, and pitch cracking. If the char is used for the production of metallurgical form coke or domestic fuel briquettes, the fuel gas can be used to provide heat for the necessary carbonization operations on the char product.

Ammonia Synthesis

The mild gasification product gas is rich in hydrogen, which can be separated from the gas stream by cryogenic, pressure-swing adsorption, or membrane separation methods, preceded by shifting of the gas over catalysts to achieve optimum hydrogen content. The hydrogen can then be used as a feedstock for a nearby ammonia synthesis plant.

Conclusions Leading to the Selection of Co-products Upgrading Methods

For all of the anticipated end uses of char, pretreatment of the coal by conventional coal cleaning methods will be required to minimize sulfur and mineral matter content. For use of the mild gasification char as a blending stock with coal for utility or industrial fuel, or for char gasification, no further upgrading would be required. If the char is to be used for metallurgical form coke production or manufacture of fuel briquettes for domestic or industrial heating, the addition of a sulfur-capture additive such as lime would probably be required. It may also be necessary to treat the char with steam to reduce the sulfur content. For the production of active char, steam treatment would also be required to increase the active surface.

Condensable hydrocarbons from mild gasification can be processed by conventional tar fractionation methods to yield light, middle, and heavy oils and a medium-soft pitch. The degree of refining of the oil fractions that will be pursued is dependent upon economic and market considerations. The light and middle oil fractions can be further distilled and refined by alkali and acid washing to recover benzene, toluene, xylenes, phenol, cresols, xyenols, heavy tar acids, pyridine bases, naphthalene, and indene as chemical feedstocks. Minimal refining of the light oils fraction can be performed to produce an octane enhancer. The remaining middle and heavy oil fractions produced by secondary coal-tar refining procedures consist primarily of creosote oils. The medium-soft pitch can be used untreated as a road and roof binder, but for the conversion to a harder grade of pitch, a thermal treatment step will be required. The medium-hard pitch resulting from thermal cracking at 1400° to 1500°F is suitable for use as a binder in the production of carbon electrodes for the aluminum industry. The cracking step also produces additional fuel gas, light oils, and pitch coke.

The fuel gas may be upgraded by conventional absorptive gas cleaning methods, although it is anticipated that a sulfur-capture additive, if used in the mild gasification reactor, could minimize the amount of cleaning that is required. Most of the fuel gas will be used onsite for satisfying the energy requirements of the mild gasification process. The use of fuel gas combustion with air for direct contact pyrolysis heat input would dilute the fuel and may preclude economic recovery of hydrogen. However, if indirect heat transfer

(or hot char recycle) is employed, the undiluted fuel gas might be processed for hydrogen recovery. Separation of hydrogen by cryogenic, PSA, or membrane separation may be performed following a catalytic shift step to maximize hydrogen content. The hydrogen can then be used for ammonia synthesis.

20WP/61089tr2/RPP

Subtask 1.3. Market Assessment

Objective

The objective of this subtask is to conduct a market assessment of the mild gasification co-products to identify the value-added uses with the potential to open new markets for coal. It is also the objective of this subtask to determine the characteristics of the value-added products so that the mild gasification process scheme, including the reactor design, could be tailored to favor their production.

Introduction

The object of this task is to assess the potential markets for the co-products that would be produced from the mild gasification process. Market-related information has been gathered from literature surveys, marketing data bases and discussions with producers of similar products and potential customers. The market assessment conducted during the project formed the basis for selecting three char utilization options. The co-products evaluated in these options were determined to be the high-value co-products in relation to the entire slate. The selection of the co-products to be evaluated has also guided the technical considerations for the development of the mild gasification process and its integration with coal preparation technology. In addition, the impact of a wide variety of upstream solid processing steps (for example, beneficiation, chemical addition, etc.) and downstream processing steps (for example, separation and upgrading of condensable products) were considered for production of commercial quality products. As a result, the mild gasification options that evolved and were assessed favor a minimum of upstream or downstream processing steps, especially for the condensable products.

Prices of chemicals and certain products were obtained from the weekly issues of the Chemical Marketing Reporter in December 1987. Product information concerning current and future supply and demand statistics, as well as production capacities, were obtained from two data bases provided by Predicasts, Inc. (Cleveland). A detailed description of these sources is given in Appendix B along with a complete listing of all market information sources used in this assessment.

Market information was collected from conversations with representatives of trade organizations and related companies. Peabody Holding Co., Inc. and Bechtel National, Inc. discussed the products and potential markets resulting from the implementation of a mild gasification process both internally and with utility and industrial representatives. IGT discussed detailed coal tar processing with representatives of the Koppers Co., the largest processor of coal tar in the United States, and also with representatives of Reilly Tar and Chemicals and Merichem, Inc. Discussions were also held with representatives of the FMC Corporation and Rexco, regarding the existing low-temperature carbonization plants.

The market assessment study recognizes that development work may be required to achieve a quality of co-products that will be commercially acceptable. However, judgments were made based upon available information and past experiences concerning the quality and potential suitability of the co-products for industrial and commercial use. The co-products that are identified to derive the value-added benefits are listed below.

a. Solid Product Options:

- Char/coal blend utility fuel
- Form coke
- Smokeless domestic fuel
- Adsorbent carbon or char

b. Condensable Products:

- Pitch (for producing road tar, roofing tar, pitch coke, graphite binder)
- Heavy creosote oil (for producing carbon black)
- Middle oils (for producing phenols, naphthalene)
- Light oils (for producing BTX)

Market Assessment of Solid Co-products

Char/Coal Utility Fuel

In order to assess the potential market for char from a mild gasification process, it is necessary to examine current and future markets for solid fossil fuels. During the first 6 months of 1987, over 400 million tons of

coal were consumed in the United States and an additional 38 million tons of domestic production was consumed in foreign markets.⁸¹ Electric utilities accounted for over 86% (344 million tons) of the coal consumed in the United States.

Domestic coal demand is projected to increase to 1,021 million tons in 1995 and 1,105 million tons in 2000 from a 1986 consumption level of 804 million tons.⁸² In the year 2000, electric utilities are expected to consume 962 million tons or 87% of the total as shown in Table I-25.

Table I-25. PROJECTIONS OF U.S. COAL CONSUMPTION⁸²

	Year					
	<u>1975</u>	<u>1980</u>	<u>1986</u>	<u>1990</u>	<u>1995</u>	<u>2000</u>
	million tons/yr					
Residential/Commercial	9	6	8	8	7	7
Industrial	64	60	77	87	95	100
Coking Plants	84	67	36	36	31	27
Electric Utilities	406	569	685	757	887	967
Total Consumption	563	703	804	888	1021	1105

Based on the current and projected markets for coal, the electric utility market will remain the primary consumer. Therefore, the electric utility market represents the single largest potential market for mild gasification char. The projected decline in domestic coke production (and consumption) may be lessened by the impact of the U.S. dollar evaluation on steel production. The decline may, however, be accelerated by impending pollution control legislation.

Utility Bituminous Coal Consumption

The mild gasification process of interest here is to be designed to utilize high sulfur, high volatile bituminous coal. As a result, the production regions and the utility consuming regions of this type of coal can be examined to define the quality and cost of coal with which the char must compete.

The mining of high sulfur, high volatile bituminous coal typically takes place in the coal-producing districts of Illinois (District 10), Indiana (District 11), Ohio (District 4), Pennsylvania (Districts 1 and 2), western

Kentucky (District 9), and West Virginia (Districts 3 and 6). Coal shipments for the first 7 months of 1987, January through July, were analyzed to identify the consuming state, delivered quantity, quality, and price for both contract and spot purchases. The average delivered quantity, quality, and cost for each producing state are shown in Table I-26. This table is compiled from the average delivered quantity, quality, and cost to each consuming state obtained from FERC reports.⁸³

Table I-26. DELIVERED QUANTITY, QUALITY, AND COST OF HIGH-SULFUR, HIGH-VOLATILE BITUMINOUS COAL FOR THE PERIOD JANUARY-JULY 1987⁸³

	<u>Tons</u> 10 ⁶	<u>Delivered Cost</u>		<u>As Received</u>		
		<u>¢/10⁶ BTU</u>	<u>(\$/Ton)</u>	<u>Sulfur</u> ----- % -----	<u>Ash</u> -----	<u>Btu/lb</u>
Illinois						
Contract	29.0	170.27	38.01	2.63	9.60	11,144
Spot	2.6	127.73	29.03	2.50	9.20	11,317
Total	31.7	166.73	37.27	2.62	9.57	11,158
Indiana						
Contract	12.5	139.59	31.14	2.53	8.95	11,146
Spot	2.0	111.95	24.70	2.45	9.54	11,038
Total	14.5	135.78	30.25	2.52	9.03	11,131
Ohio						
Contract	15.8	170.44	39.95	3.26	11.40	11,755
Spot	3.4	116.92	27.87	2.73	10.71	11,855
Total	19.2	160.95	37.81	3.16	11.28	11,773
Pennsylvania						
Contract	26.8	151.92	37.94	1.75	13.11	12,462
Spot	8.4	129.19	32.44	1.80	10.87	12,507
Total	35.2	146.51	36.63	1.76	12.58	12,473
W. Kentucky						
Contract	22.5	135.93	31.34	3.19	11.19	11,458
Spot	5.3	115.28	27.58	3.03	10.63	11,935
Total	27.8	131.97	30.62	3.16	11.08	11,550
West Virginia						
Contract	20.4	151.94	38.47	2.43	10.46	12,563
Spot	3.7	122.69	31.34	1.95	10.69	12,678
Total	24.1	147.47	37.38	2.36	10.50	12,657

The available information on the quality of coal utilized in the electric utility market does not provide values for volatile matter content, Hardgrove grindability index, ash fusion temperatures, and minimum size restrictions.

These values will play an important part in determining the acceptability of char in the electric utility market.

Coal Supply Agreement Specifications

In order to further define the quality specifications for a char to compete in the electric utility market, Peabody Development Company surveyed the coal quality specifications in its major coal supply agreements. The survey encompassed 16 major coal supply agreements covering obligations to supply approximately 28 million tons of high sulfur, high volatile bituminous coal. Table I-27 presents the results of that survey.

Table I-27. SURVEY OF MAJOR COAL SUPPLY AGREEMENT SPECIFICATIONS

<u>Specification</u>	<u>Range (As Received)</u>
Tonnage Surveyed, 10 ⁶ ton/yr	28
Moisture, %	7.5-1.6
Fixed Carbon, %	43-47
Volatile Matter, %	32-36
Ash, %	9.7-18.0
Sulfur, %	2-5
Heat Content, Btu/lb	10,400-12,500
Ash Fusion Temperature, °F	1950-2450
Chlorine, %	0.08 max
Hardgrove Grindability Index	48-55
Base-Acid Ratio	0.3
Size Distribution, %	
2-in. X 1/4-in.	64
1/4-in. X 60 mesh	30
60 X 100 mesh	6
-100 mesh	0

The specification of values for fixed carbon and volatile matter appeared primarily in newer contracts. This trend is indicative of the electric utilities' ever-increasing awareness of the impact of fuel quality on power generation costs.

To further illustrate the quality parameters that are acceptable to the electric utility industry, Appendix D contains a complete analysis of an Illinois No. 6 Seam coal and Pittsburgh No. 8 Seam coal. Analyses are provided for both raw (run of mine) coal and washed coal.

Modes of Transportation

Another important factor that will impact the market acceptability of a fuel is the mode of transportation by which it is delivered. Table I-28 summarizes the origin, method of transportation, and consumer of the high-sulfur bituminous coal produced in the states of Illinois, Indiana, western Kentucky, Ohio, Pennsylvania, and northern West Virginia for the period January through June 1987. Electric utilities consumed 96% of the coal delivered from these and 41% of that coal moved by rail. As indicated in Table I-28, there is ample opportunity for the char to move by rail, truck, or water to the consumer.

Char Quality

Having examined the quality of the coal with which char must compete in the solid fossil fuel market, the quality of the char must next be examined. The review of available literature produced only a limited amount of quality data for char produced under mild gasification conditions. Jones *et al.* published quality data for char produced from the FMC COED process.^{14,45} The qualities of COED char produced from Illinois No. 6, a blend of western Kentucky No. 9 and No. 14 and Pittsburgh No. 8 coals are shown in Table I-29. The COED process has four stages of pyrolysis after which the char is available for various uses. The second and third stage char analyses are shown in Table I-29 in an attempt to match the temperature conditions of mild gasification, 930° to 1200°F (500° to 650°C). A comparison of the char characteristics relative to the coal shows no significant change in the sulfur content, a moderate reduction in the Btu, an increase in the ash content, and a significant loss of volatile matter.

Khan has reported a similar comparison for char produced from Illinois No. 6 and Pittsburgh No. 8 coals utilizing a bench-scale mild pyrolysis process.⁷⁸ The analyses are shown in Table I-30. Khan, in his work, mixed calcium oxide with the coal prior to charring, in an attempt to produce a low-sulfur condensable product. The resultant impact on the char was to increase its sulfur and ash content.

Market Acceptance

The acceptance of the char as a replacement for coal will depend on operational, emission compliance, and economic considerations. From an

Table I-28. DOMESTIC DISTRIBUTION OF U.S. COAL BY ORIGIN, METHOD
OF TRANSPORTATION AND CONSUMER: JANUARY THROUGH JUNE 1987

<u>Origin</u>	<u>Electric Utilities</u>	<u>Coke Plants</u>	<u>Other Industrial</u>	<u>Residential & Commercial</u>	<u>Total</u>
Illinois	26,648	1,001	1,816	123	29,589
Rail	15,819	996	471	5	17,291
Truck	1,464	--	1,046	110	2,621
Water	8,305	4	281	2	8,592
Other	1,060	--	18	6	1,085
Indiana	13,816	--	2,119	212	16,188
Rail	7,841	--	1,000	--	8,841
Truck	2,859	--	773	208	3,841
Water	3,115	--	345	3	3,463
Other	2,859	--	775	209	3,884
w. Kentucky	20,681	--	906	50	21,732
Rail	6,240	--	273	--	6,514
Truck	2,491	--	293	46	2,830
Water	10,596	--	339	3	10,939
Other	3,845	--	293	1	1,450
Ohio	16,046	9	1,295	294	17,652
Rail	3,276	--	9	10	3,294
Truck	3,528	9	1,258	280	5,075
Water	5,347	--	24	3	5,175
Other	4,095	--	4	1	5,108
Pennsylvania	26,737	3,863	2,733	577	34,110
Rail	12,197	2,207	846	25	15,275
Truck	5,656	29	1,624	479	7,788
Water	2,560	1,626	221	1	4,407
Other	6,324	--	43	1	316
n. W. Virginia	18,523	--	1,515	124	20,167
Rail	7,416	--	775	43	8,234
Truck	1,320	--	488	79	1,888
Water	7,268	--	242	--	7,509
Other	2,519	--	10	1	2,536

Table I-29. ANALYSIS OF SECOND- AND THIRD-STAGE FMC COED CHAR^{14,45}

	Illinois No. 6			Western Kentucky No. 9 and No. 14			Pittsburgh No. 8		
	Coal	Stage 2 Char	Stage 3 Char	Coal	Stage 2 Char	Stage 3 Char	Coal	Stage 2 Char	Stage 3 Char
Moisture, wt %	9.0*	1.1	0.9	3.5*	1.1	1.1	1.8**	0.1	0.2
Proximate, wt % (dry)									
VN	38.5	12.1	9.3	38.0	13.8	10.9	38.3	23.8	10.6
FC	50.0	61.6	67.6	53.3	73.4	73.0	52.7	66.5	76.9
Ash	11.5	26.3	23.1	8.7	12.8	16.1	9.0	9.7	12.5
Ultimate, %									
C	67.3	63.9	63.8	70.3	74.8	74.1	73.0	73.8	75.3
H	4.9	1.8	1.1	5.2	2.5	2.0	5.2	3.8	2.8
N	1.3	1.1	0.8	1.5	1.5	1.6	1.3	1.3	1.4
S	4.3	4.6	6.3	3.1	2.9	3.3	4.3	4.1	4.0
O	10.7	2.3	0.0	11.2	5.5	3.0	7.2	7.3	4.0
Ash	11.5	26.3	28.0	8.7	12.8	16.0	9.0	9.7	12.5
HHV Btu/lb (dry) (calculated)	12,230	10,300	10,060	12,990	12,240	12,010	13,460	13,190	13,300
Density, lb/ft ³	48.8	27.5	27.5	45.5	29.3	31.3	N/A	24.8	23.8
Size Consist, cumulative %									
Tyler Mesh									
14	20.2	9.0	3.7	10.1	4.0	3.5	13.2	6.1	12.2
28	57.2	37.7	40.0	35.2	37.4	35.6	42.9	36.3	50.3
48	75.9	66.0	67.9	57.0	67.8	66.7	64.6	57.9	70.5
100	86.2	84.4	83.1	73.0	86.4	85.2	79.0	74.0	81.5
200	92.2	94.3	92.4	85.1	94.4	93.5	82.6	85.0	85.6
325	95.2	97.7	96.1	92.1	97.8	97.4	93.4	93.8	93.7
Pan	99.7	99.8	99.6	100.0	100.0	100.0	100.0	100.0	100.0
Process Temp, °F	--	800	990	--	765	885	--	725	840

* As fed to Stage 1.

** As received.

Table I-30. PROPERTIES OF COALS AND MILD GASIFICATION CHARs FROM ILLINOIS NO. 6 AND PITTSBURGH NO. 8 COALS⁷⁸

	<u>Illinois No. 6</u>		<u>Pittsburgh No. 8</u>	
	<u>Coal</u>	<u>Char</u>	<u>Coal</u>	<u>Char</u>
Moisture, wt %	4.05	1.25	0.57	
Proximate, wt % (dry)				
FC	53.4	74.5	52.2	76.3
VM	37.8	15.8	40.1	13.6
Ash	<u>8.8</u>	<u>9.7</u>	<u>7.7</u>	<u>10.1</u>
Total	100.0	100.0	100.0	100.0
Ultimate				
C	69.3	80.5	77.2	75.8
H	4.8	2.8	5.0	2.8
N	1.3	2.3	1.4	1.9
S	3.2	3.0	2.0	1.8
O	12.6	1.7	6.7	7.6
Ash	<u>8.8</u>	<u>9.7</u>	<u>7.7</u>	<u>10.1</u>
Total	100.0	100.0	100.0	100.0
HV, Btu/lb (dry)	13,052	12,292	14,056	12,554
Temperature, °F	--	932	--	932

operational perspective, the combustion characteristics of the char will make it a less desirable fuel. The significant decrease in volatile matter could potentially cause a decrease in combustion efficiency (increase in carbon loss) and problems with flame stabilization requiring the firing of auxiliary fuel at reduced combustion rates. In addition, the increased ash content could increase the potential for slagging, fouling, and erosion. Similarly, the ash handling system could be adversely affected, and decreases could be experienced in the lives of the ash disposal facilities. Finally, if the gasification process shifts the size consist of the char toward more fine material, which reduces its mechanical strength or increases its oxidation reactivity, increased problems from unloading, handling fugitive dust, and storage stability could be encountered.

From an emissions perspective, both the sulfur and particulate emission potential could increase on a basis of weight per million Btu of heat input. The particulate emission potential for the Illinois No. 6 coal reported by Khan is 5.06 lb/10⁶ Btu, while the char potential emission rate would be 7.89 lb/10⁶ Btu.⁷⁸ This represents a 56% increase in the amount of ash fed to

the furnace and particulate control equipment. Depending on how the sulfur is split between the char and the condensables, a similar increase in the sulfur emission potential of the char could result. However, if lime is used as a sulfur capture additive, it is left with the char and it is possible that during combustion with a large air excess, the lime could combine with SO₂ to form stable calcium sulfate, which is acceptable for normal disposal.⁸⁴ Calcium sulfite resulting from restricted air combustion could require additional oxidation.

The char will be a less desirable fuel than coal because of the relative loss of volatile matter and increased ash and sulfur content. Kolstad et al. have examined the impact of two of these parameters -- volatile matter and sulfur content -- on the utility market for Illinois coal.⁸⁴ These investigators focused their work on char and the impact of reduced volatile matter and sulfur on the consumer's willingness to pay for the difference in quality. Actual utility coal transactions for the year 1985 as reported by the Federal Energy Regulatory Commission (FERC) were statistically analyzed. Kolstad et al. reported in their preliminary results that the value of a sulfur reduction of 1 pound per million Btu ranges from about \$0.70/10⁶ Btu per pound of sulfur per million Btu to slightly more than \$1.00/10⁶ Btu per pound of sulfur per million Btu. Thus, the premium or penalty applied to a coal or char containing sulfur would be the product of the value of the sulfur reduction and the sulfur content; that is,

$$\left[\frac{\$0.70-1.00/10^6 \text{ Btu}}{1 \text{ lb S}/10^6 \text{ Btu}} \right] \cdot \left[\frac{1 \text{ lb S in fuel}}{10^6 \text{ Btu}} \right]$$

To overcome the lack of volatility information in the FERC or other transaction information, Kolstad et al. examined all electric utilities that purchased Illinois coal in 1985. A survey questionnaire was sent to a subset of those plants (77 power plants) and responses were received from 61 plants. A copy of the survey is shown in Appendix E. Each plant operator was given the specifications for a reduced sulfur and volatile matter fuel. Sulfur specifications were either 0.45 lb/10⁶ Btu, 0.95 lb/10⁶ Btu, or 1.78 lb/10⁶ Btu. Volatile matter specifications were either 15.12%, 25.14%, or 35.26%. The preliminary results indicated that a change of 2.5% in volatile content (that is, 27.5% to 25.0%) was valued at \$0.08/10⁶ Btu. (It should be noted, however, that Occidental Flash Pyrolysis char was assessed as having combustion properties similar to or superior to the parent coal.)

The survey also asked for the respondent to provide boundary (maximum or minimum) procurement specifications for each generating unit at the power plant. The results of the survey are shown in Table I-31. The mean volatile matter specification was 43% by weight (dry) and the minimum was 19% by weight (dry). Of the 48 responses on volatility, only five indicated a specification below 25% by weight (dry) volatile matter product in the survey, only seven indicated a willingness to purchase the fuel, and, in most instances of a willingness to purchase, a significant sulfur and cost reduction also was required.

Table I-31. SUMMARY OF CHAR MARKET SURVEY RESULTS⁸⁴

<u>Specification</u>	<u>Number</u>	<u>Mean</u>	<u>Min</u>	<u>Max</u>
Minimum Btu/lb (moisture free)	55	11450	7700	13889
Maximum Sulfur Content (as received, measured lb/MM Btu)	61	2.5	0.59	6.8
Maximum Moisture Content (as received %)	61	16%	6%	36%
Minimum Volatile Matter (by weight, moisture free)	48	32%	19%	44%
Maximum Chlorine (by weight, moisture free)	28	0.21%	0.03%	0.50%
Size Dispersion (Maximum % less than 1/4 in.)	44	41%	3%	85%
Minimum Hargrove Grindability Index	54	49	40	63
Maximum Ash Content (by weight, moisture free)	59	12%	6%	33%
Minimum T ₂₅₀ (ash fusion) Temperature (°F)	40	2174	1900	2660
Maximum T ₂₅₀ (ash fusion) Temperature (°F)	25	2500	2100	2920
Maximum Base/Acid Ratio of Ash	17	0.64	0.25	2.33
Maximum Na ₂ O as % of Ash Mineral Analysis	23	1.34	0.40	3.0
Maximum % Alkaline as Na ₂ O, Dry Basis	8	0.32	0.09	0.65

The survey results from Kolstad et al. indicate that the volatility of the fuel is very important to the electric utility consumer. Current procurement specifications for those plants surveyed would not allow a volatility

below 19% by weight (dry), but for most a volatile content above 30% was considered desirable. A number of consumers would only consider a low volatility product if it was also a low sulfur and low cost product.

It is important to note that Kolstad et al. indicated that the results from the transaction analyses and survey should be regarded as preliminary, and additional efforts to improve the analyses and survey are being undertaken. An example of an area needing further review is the fact that the survey did not substantiate the sulfur premium evidenced in the transaction analysis. However, based on these preliminary results, there is compelling evidence of a willingness to pay a premium or penalty for the volatile and sulfur content of coal or char.

In order to provide confirming input on the operational, emission compliance, and economic considerations related to the market acceptance of char, a major electric utility that burns a substantial amount of high sulfur, high volatile bituminous coal was visited. During the visit, utility representatives from the fossil fuel procurement, environmental affairs, power plant operations, and corporate planning functions were apprised of the mild gasification process and the resultant char quality produced from Illinois No. 6 coal as reported by Khan.⁷⁸ The utility representatives were asked their opinion of problems that might occur if char was to be utilized in their existing units. Their concerns were centered in the areas previously discussed, combustion efficiency, emission compliance, and material handling and disposal. Volatility and sulfur content were the major areas of concern. In addition, it was their opinion that a test burn of the char in the particular unit in which it was to be utilized would be necessary before it could be judged acceptable for procurement.

The fuel procurement representatives indicated that the utility had a procedure that was utilized to evaluate fuels proposed for procurement or "fuel bids" as they are commonly termed. The factors used in evaluating bids include --

- Delivered price per million Btu
- Fuel quality and specifications
- Terms and conditions
- Delivery schedule and charges

- Reliability of the transportation system.

Coal and char would be evaluated on an adjusted cost per million Btu basis to ensure that bids are compared on an equal basis. The bid price is adjusted for transportation costs, taxes, quoted Btu, and ash and moisture contents. The adjustments to the cost related to ash and moisture content vary from plant to plant, are subject to periodic updates, and are based on historic plant operation and maintenance costs plus current economic parameters.

The price the utility pays for fuel is also subject to premiums or penalties if the fuel's Btu, ash, and moisture deviate from the guaranteed values. If the delivered fuel is of a higher quality, the utility will pay a specified premium to the supplier. If the delivered product is of a lower quality than guaranteed, a penalty in the form of a reduced price is paid to the supplier. If the quality falls below the minimum guaranteed quality, the utility can reject the shipment and refuse payment. Examples of the adjusted fuel cost and an example of the premium/penalty payment computations for moisture and ash content are described in Appendix F.

Other char characteristics that relate to ease of handling and shipping may also impact price. These include: mechanical strength affecting fines generation, bulk density, and oxidation reactivity relating to storage stability.

Marketing Strategy

Based on the review of the current and projected electric utility markets for high sulfur, high volatile bituminous coal, it is apparent that char from a mild gasification process will not be the fuel of choice based on its operational and emission potential when competing with coal. Char would only be competitive if it has a significantly lower sulfur content or a significantly lower price than coal or both. However, there are two possible marketing strategies that may substantially improve the market acceptability of mild gasification char.

Using current and projected electric utility markets to judge the acceptability and competitiveness of char assumes that current coal supplies will remain acceptable and competitive. There is, however, a reasonable expectation that this may not be the case due to a change in allowable sulfur

emissions as a result of enactment of acid deposition control legislation. Proposals currently being considered in Congress call for utility SO₂ emission reductions of 10 to 12 million tons from 1980 levels. Under one such bill, S.1894, passed by the Senate Environment and Public Works Committee, the state-wide average SO₂ emission limits for fossil-fuel-fired utilities would be equal to or less than 0.9 lb/10⁶ Btu.⁸⁵ During 1986, the states east and bordering the Mississippi River produced over 575 million tons of bituminous coal, or 65% of the nation's total production. Yet, only seven-tenths of 1% of that production, or a little over 4 million tons, was of a quality that would comply with the 0.9 lb/10⁶ Btu level. For the entire United States, only 17% of the 1986 production would comply with the Senate Committee bill's emission limit.

In examining the impact that a 12 million tons SO₂ reduction would have on high sulfur coal production, ICF Incorporated has estimated for the Environmental Protection Agency that 88.3 million tons of production would be displaced from Northern Appalachia and the Midwest.⁸⁶ The Congressional Budget Office has estimated that displacement will range from 49 to 67 million tons from the same producing regions.⁸⁷ In a similar analysis, Temple, Barker and Sloane, Inc. estimated for the Edison Electric Institute that coal switching would involve the replacement of high sulfur coal with between 54 and 107 million tons of low sulfur coal primarily from the West.⁸⁸ The effect on the price differential between eastern low sulfur coal and high sulfur coal has been estimated by Energy Venture Analysis, Inc., for the Electric Power Research Institute, to be between 16 and 18 dollars per ton (1985 dollars per ton f.o.b. mine) for a 10 million tons reduction in utility SO₂ emissions.⁸⁹

The effect of enactment of acid deposition control legislation will be to dramatically change the solid fossil fuel market. Traditional fuel supplies may no longer be acceptable and utilities will be willing to pay more for a low sulfur fuel. Mild pyrolysis char from high sulfur coal also may not be acceptable as fuel unless its sulfur content can be reduced. This may require a combination of deep-cleaning the feed coal for mineral sulfur removal in conjunction with posttreatment of the char with steam or other reagents for reduction of organic sulfur. A reduced sulfur content char might then become an alternative to a more costly low sulfur coal.

The vast majority of high sulfur, high volatile bituminous coal is subjected to some form of coal preparation prior to shipment. Coal preparation typically consists of sizing the coal (crushing and screening), gravitational separation of the coal and mineral matter utilizing water or heavy media, and the dewatering of the clean coal. The preparation facility will generally have different circuits treating different sizes of raw coal -- coarse, middlings, and fine. The amount of fine coal produced is dependent on coal characteristics, mining methods, and the degree of sizing.

The quality of the various size products will vary because crushing to small sizes produces more liberation of mineral matter, but it also presents more surface area allowing for retention of water. Table I-32 shows the quality of the various sized products produced in a preparation plant processing over 5 million tons per year of run-of-mine Illinois No. 6 coal. The smaller size fractions are significantly higher in moisture content, and thus lower in Btu content. As a result, the fine product disproportionately reduces the heating value of the total coal product. In addition, as indicated in the previous discussions, the amount of fines in the product can be a contractual issue with the consumer who wishes to avoid material handling problems. As a result, the amount of fines in the final product and its quality are constant operating constraints on the preparation process.

Table I-32. PREPARATION PLANT PRODUCT QUALITY

<u>Product Size</u>	<u>Moisture</u> -----	<u>Ash</u> wt %	<u>Sulfur</u> -----	<u>Btu/lb</u>
2-in. X 1-in.	11.35	10.24	3.11	11,111
1-in. X 2 mm	12.45	9.20	2.91	11,117
2 mm X 1 mm	13.31	9.89	2.93	10,877
1 mm X 100 mesh	18.72	10.96	2.75	9,980
2-in. X 0-in.	13.20	10.37	2.99	10,871

Integration of the mild gasification plant with the preparation plant can address this fine coal problem. The minus 1/2-in portion of the preparation plant coal product would be segregated to feed the mild gasification plant. Figure I-76 shows the material flows for an integrated process for a 4 million raw ton per year preparation plant. This is a common size of preparation plant. There are 13 plants this size or larger located in the state of

Illinois.⁹⁰ For this configuration, the preparation plant is assumed to yield 70% by weight of product coal and the product coal has the size distribution shown in Table I-33.

Table I-33. PRODUCT COAL SIZE DISTRIBUTION

<u>Size</u>	<u>% of Product</u>
2-in. X 1/2-in.	40.0
1/2-in. X 1/4-in.	22.5
1/4-in. X 0-in.	37.5

Utilizing the material balance and the quality of Illinois No. 6 coal and char reported by Khan,³⁸ the quality of the char/coal blend can be computed as shown in Table I-34. In addition, by utilizing the utility ash and moisture price adjustments from the utility procurement procedures and the volatile matter and sulfur premium/penalty factors from Kolstad *et al.*,⁸⁴ the adjusted price of the coal, char, and blend can be computed as shown in Table I-34. Based on these factors and assuming a \$1.20 per million Btu f.o.b. mine price for coal, a utility would only be willing to pay 45% of the value of the coal for char (\$0.54/10⁶ Btu). However, the utility would be willing to pay 88% of the value of the coal for the char/coal blend (\$1.06/10⁶ Btu).

Table I-34. COAL AND CHAR QUALITY AND PRICE FOR ILLINOIS NO. 6 COAL

<u>Specification</u>	<u>Coal</u>	<u>Char</u>	<u>Blend</u>
Moisture, wt %	4.05	1.25	3.31
Proximate Analysis, wt % dry			
FC	53.4	74.5	59.0
VM	37.8	15.8	31.9
Ash	8.8	9.7	9.0
Total	100.0	100.0	100.0
Sulfur, wt % dry	3.2	3.0	3.1
Btu/lb (dry)	13,052	12,275	12,845
Adjusted f.o.b. Mine Price			
\$/ton	30.00	13.12	26.23
\$/10 ⁶ Btu	1.20	0.54	1.06
% of Coal Price	100	45	88

The "willingness to pay" value of the char/coal blend is conservative because it does not account for other benefits of blending the coal and char. First, hot (1200°F) char will initially be mixed with the 1/2-in. X 1/4-in. fraction of the clean coal to cool the char. This will heat up the coal causing the release of moisture and increasing the Btu value of the blend and ultimately the total product. Secondly, during this mixing of hot char and fine coal, the coal will release tars as well as moisture. The tar may promote the agglomeration of the fine char and coal particles and decrease the percentage of -1/4-in. material. Although the extent to which either of these benefits will occur remains to be verified, preliminary heat balance estimates for the integrated process indicate that there is sufficient excess heat in the hot char (1200°F) to 1) completely dry the 1/2-in. X 1/4-in. coal product that would be blended with the char and 2) raise the coal to a temperature of 650°F (high enough for tar liberation). Furthermore, the heat balance for the mild gasification process indicates that there is sufficient heat for drying the 2-in. X 1/2-in. clean coal product, reducing its moisture content by as much as 4 percentage points (that is, from 12% to 8%). The beneficiation of these two product streams will increase the Btu content of the char/coal blend and make its market value approach or even exceed the value of the feed coal.

Form Coke

A second major market for coal is coke. Coke is primarily used for blast furnace iron ore reduction, but has other metallurgical and chemical uses. The second option for marketing the co-product char from the mild gasification process would be to produce a form coke to service the steel industry.

Status of the American Steel Industry

The United States steelmaking industry has been experiencing far reaching changes during the past 10 years. The decline in steel production which started in 1979 as a relatively mild capacity adjustment continued and now seems to have stabilized at about 60% of the 1976 capacity (Table I-35).

The coke consumption for the ironmaking operation (Table I-36) has undergone similar changes and decreased from the high level of domestic production capacity of about 80 million tons in 1976 to about 25 million tons in 1986 and 1987. An increasing fraction of the blast furnace coke used in the United States is expected to be imported. This is caused mainly by the

Table I-35. WORLD PIG IRON PRODUCTION STATISTICS

	(Thousand Metric Tons)									
	1976	1977	1978	1979	1980	1981	1982	1983	1984	1985
Australia	7,308	6,733	7,280	7,759	6,976	6,740	5,953	5,062	5,324	5,599
Belgium	9,866	8,912	10,128	10,858	9,900	9,809	7,831	8,068	9,011	8,749
Brazil	8,170	9,380	10,043	11,594	12,685	10,791	10,827	12,945	17,230	18,961
Canada	10,033	9,661	10,338	10,906	10,893	9,743	8,000	8,567	9,643	9,665
FR of Germany	31,629	28,784	29,939	35,181	33,873	31,876	27,621	26,598	30,203	31,531
Japan	86,576	85,886	78,589	83,825	87,041	80,048	77,655	72,936	80,403	80,569
Netherlands	4,267	3,922	4,613	4,814	4,329	4,600	3,617	3,747	4,926	4,819
United Kingdom	13,713	12,135	11,365	12,761	6,264	9,470	8,327	9,477	9,487	10,382
United States	78,808	73,780	79,541	78,929	62,343	66,742	39,281	44,208	47,087	45,764
USSR	104,400	106,500	110,000	108,300	107,282	107,766	106,723	110,453	110,893	109,977

These figures exclude direct reduce iron and blast furnace ferro-alloys.

Table I-36. U.S. CONSUMPTION OF METALLURGICAL COKE
(Million tons/yr)

	<u>1980</u>	<u>1981</u>	<u>1982</u>	<u>1983</u>	<u>1984</u>	<u>1985</u>	<u>1986</u>
Production	46.1	42.8	28.1	25.8	30.6	28.7	25.5
Imports	0.66	0.53	0.12	0.04	0.58	0.58	0.33

shutting down of coke ovens, in turn primarily due to the aging of U.S. coke batteries and the increasing cost of meeting environmental regulations. Of the existing coke ovens, 50% are older than 20 years and many have long exceeded their projected life expectancy (Table I-37). There appears to be no plans for major building of new coke batteries or for rebuilding old units, although a few new units have been built.⁹¹

Table I-37. AGE PROFILE OF U.S. COKE OVENS AS OF DECEMBER 31, 1987⁹¹
(Estimated as Percent Total)

<u><5 yrs</u>	<u>6-15 yrs</u>	<u>16-25 yrs</u>	<u>26-30 yrs</u>	<u>>30 yrs</u>
7.2	14.4	27.8	22.3	28.3

Note: 50% are older than 20 years.

The U.S. production of basic carbon steel rests on the oxygen process which in turn requires a supply of liquid iron smelted from iron ores in the conventional coke blast furnaces.

It is expected that the production of oxygen process steel will hover around 47 to 50 million tons/yr into the 1990's provided the blast furnace divisions are supplied with sufficient metallurgical coke.

The improving productivity and financial situation of the steel industry, contributed to by the decline in the U.S. dollar, might bring about some changes in the building plans for new coking capacity. So far only a few new coke batteries have been built. More have been shut down. New batteries are expensive to build and thus represent a major expenditure. The estimated construction costs range from \$300 to \$350 per annual ton of coke produced.

In addition, the air quality control regulations of the U.S. Environmental Protection Agency (EPA) and individual state environmental departments are making it very difficult for conventional coke batteries to

meet the air quality requirements. Thus, the future of the existing and new by-product coke batteries in the United States is questionable at best.

The United States coke requirements are currently estimated to be about 24 to 27 million tons/yr for the next 10 years. However, the United States production capacity for coke is projected to fall to about 10 million tons by 1991. With no new coke ovens to be built, imports would have to make up the difference, as shown in Figure I-77.

The United States steelmakers could obviously import more coke from abroad saving construction capital but this will become counterproductive for several reasons. The important issues are as follows:

- Loss of coke production capacity and dependence upon foreign suppliers for a strategically important raw material (without which production of high quality steel is not possible).
- Loss of gaseous and liquid by-products of the coking operations
- Outflow of dollars to pay for imports
- Further cutbacks in the production of U.S. coal.

A possible solution to live with the reduced availability of U.S. coke is to practice processes where liquid iron could be produced without coke, such as the Corex process. In this process, medium volatile coal is reacted with oxygen, thus avoiding the need to first carbonize the coal to coke in by-product coking batteries.⁹²

It is also possible to produce the coke by means of modified coking processes -- such as the wide oven designed by the Bergbau-Forschung organization of Germany or a modified beehive coking method such as the Thompson nonrecovery (by-product destructive) oven. However, these processes still consist of coking chambers with many of the economic and environmental problems of conventional coking batteries.

The most promising innovation is the concept of form coking, consisting of the production of uniformly sized briquettes, made essentially of devolatilized char and carbonaceous binders and subsequently subjecting the briquettes to high-temperature carbonization. This project will investigate the feasibility of producing binderless form coke. By mixing the hot char with raw coal, the coal would heatup and become soft. The tar resulting from coal devolatilization could serve as the binder for briquetting the char-coal mixture.

Figure I-77. PROJECTED SUPPLY OF METALLURGICAL COKE FROM DOMESTIC COKE OVENS AND IMPORTS

Form Coke Processes

Many form coking processes have been proposed and patented, although only a few have been developed to the commercial stage. Six of the most significant processes that have actually produced enough coke for blast furnace trials, are listed below and described in detail in Appendix G --

1. Eschweiler Bergwerkverein (Ancit), Germany
2. Bergbau-Forschung-Lurgi (BFL), Germany
3. Houilleres du Bassin de Nord (HBN), France
4. Sapozhinkov -- Ukrainian Institute of Coal Research, USSR
5. Didier-Keihan Rentan-Sumitomo Metal (DKS), Japan
6. FMC Corporation (FMC), United States.

One other process, the Consol-BNR Coke Pellet Process, progressed to the demonstration plant stage; however, the work was suspended before any significant blast furnace trials could be run. Pertinent features of these processes are summarized in Table I-38.

The potential benefits of producing form coke are essentially as follows:

- A. The use of uniformly sized and shaped form coke briquettes in place of by-product oven coke is expected to increase blast furnace productivity and lower the coke rate, possibly by as much as 100 pounds of coke/ton of hot metal. Using data generated by Inland Steel's plant energy model together with conceptual design data on the form coke process, it has been calculated that a 100 lb/ton decrease in the coke rate would result in a 5-1/2% decrease in the total energy requirement per ton of raw steel produced at the Indiana Harbor Works. If extended to the entire steel industry in the U.S., coal savings on the order of 8 million tons/yr could be projected.⁹²
- B. In the by-product oven process, a closely controlled blend of metallurgical coals must be used to charge the ovens. In contrast, the FMC coke process can use a single coal or blend of coals which can be either coking or noncoking coals. Hence, by utilizing this process, a much larger range of coals and, in turn, a much larger reserve of coals become available for producing coke for blast furnace use, thus reducing the dependence of the steel industry on metallurgical coal, an increasingly critical fuel.
- C. The cost of mining good metallurgical coal in the U.S. is often quite high. In contrast, many of the nonmetallurgical coals that are suitable for the FMC form coke process can be mined more cheaply, and the lower mining costs ultimately result in lower coke costs. Furthermore, it is likely that overall average energy expended on mining these coals would be decreased.

Table I-38. PERTINENT FEATURES OF VARIOUS FORM COKE PROCESSES

Process	Coals Required	Thermal		Requires Binder	Forming		Thermal Posttreatment
		Pretreatment					
Ancit	25% Coking 75% Noncoking	Yes		No	Hot Briquetting at 850°F		No
BFL	35% Coking 65% Noncoking	No		No	Hot Briquetting at 850°F		Optional
HBN	15% Noncoking 85% Coking	No		Yes	Cold Briquetting with Supplemental Binder		Yes
Sapozhnikov	100% Weakly Coking Coal	Yes		No	Hot Briquetting		Yes
DKS	20% Noncoking 80% Coking	No		Yes	Cold Briquetting with Supplemental Binder		Yes
FMC	100% Noncoking	Yes		Yes	Cold Briquetting with Internally Generated Binder		Yes

- D. As a result of less dependence on metallurgical coals, the coke requirements of steelmakers could be met fully with coals closer to their plants, resulting in dollar and energy savings in transportation (0.5 to 1.0 million Btu/ton of coal for 300 miles).
- E. A large but unknown quantity of coal has either been left in metallurgical coal mines or mined out and discarded because it is too oxidized to be used to make coke. This coal could be used to make form coke. Thus, the amount of Eastern coals usable for coke-making would be expanded and the productive lives of many Eastern metallurgical coal mines would be extended. This could postpone job relocations and help to defer new mine construction with its attendant capital, energy, and environmental costs.
- F. At the present time, by-product ovens present the most serious air pollution problem facing the steel industry. Strict OSHA regulations to protect coke plant workers have been put into effect and have necessitated major efforts and expenditures by the steel companies. The EPA is currently investigating the potential health effects of coke plant emissions on the general population and is considering additional stringent regulations. The by-product oven is a refractory structure operating under positive pressure and, as a result, fumes can escape through any cracks or openings. When by-product ovens are sealed, containment of emissions is relatively good. However, whenever the oven is opened, which must occur every 12 to 24 hours, substantial energy must be expended to either prevent fumes from escaping or recapture them after they exit the oven. In contrast, a process like the FMC form coke process is able to control and contain emissions. It is a continuous, closed process with coal entry and exit from the steel shell carbonization vessels controlled by effective seals. The process recommended for development in this project will meet these criteria.
- G. By-product oven coke is normally quenched from the incandescent state using thousands of gallons of water, which results in steam being discharged to the atmosphere with entrained fine coke particles and fumes. This quenching operation is recognized not only as a major energy loss, but also as a pollution source. In contrast, form coke, after coking, is cooled in an enclosed kiln or shaft with countercurrent flowing gases which cool the product and permit the reuse of a portion of the energy which would otherwise be lost, a feature which is much more practical with a continuous process. The gases can readily be contained and cleaned to prevent air pollution.
- H. The potential exists for form coke plants to be constructed close to coal supplies, where form coke could be produced for export. This approach would not only provide a more valuable product for export than metallurgical coals, thus having a favorable impact on the balance of trade, but also make more jobs and by-products available in the U.S.
- I. A significant percentage of the existing coke batteries of the U.S. are at an age such that a massive replacement effort will be necessary in the period 1988 to 2000. Furthermore, present coke import data indicate a lack of foreign coke-making capacity to fully support coal-based steelmaking operations in the U.S. If a viable form coke process for producing a blast-furnace-quality product is successfully demonstrated,

immediate and extensive application of the form coke process technology in the steel industry of the U.S. can be expected.

- J. Form coking processes produce as a by-product, condensable hydrocarbons and gaseous fuels with gas heating values ranging from 150 (FMC) to over 600 Btu's (BFL) per cubic foot. This represents 20% to 25% of the heating value of the original coal and should be sufficient for in-plant energy needs.

Form coke represents a desirable fuel material for the following three basic applications:

1. Metallurgical coke replacement -- potential market approximately 25 million tons/yr
2. Chemical coke (production of sugar, ferro alloys, phosphorus) -- potential market approximately 200,000 tons/yr
3. Domestic fuel (smokeless) -- market approximately 1.5 million tons (1988), which is expected to increase to >10 million tons in the 1990's because of growing local shortages of natural gas, anthracite, and wood.

To enter the major metallurgical market for blast furnace use, the coke must meet acceptable standards for 1) size consist and mechanical strength, 2) density and reactivity, and 3) sulfur and ash content. The utility of char from a high-sulfur bituminous coal will depend on meeting the first and second standards, and by compensation in price for probable deficiencies in the third standard. It is possible that sulfur content could be compensated for by the addition to the coke briquette of small amounts of lime or lime-dolomite blend. This would reduce the quantity of extra limestone charge to the furnace that would otherwise be required.

Several trials of lime addition to form coke were carried out in the 1960's by the BBF laboratories in Essen, Germany, with very promising results. Lime addition would supplement the present practice of blowing lime into the hot iron after the blast furnace to eliminate residual sulfur and other contaminants.

Coke Prices

The average price in 1986 for import and export coke was \$78 to \$80 per ton. These prices are f.a.s. (free alongside ship). Prices had been higher in 1982 when coke demand was higher. Wierton Steel reportedly paid \$110/ton in 1982 for metallurgical coke imported from Japan.⁹³ Also, McLouth Steel and Sharon Steel Corp. have paid similar prices, as these companies do not have

any of their own coke batteries. These costs may have increased significantly with the devaluation of the U.S. dollar relative to foreign currencies, particularly with respect to the Japanese Yen.

The Rexco low-temperature carbonization plant in Nottinghamshire, U.K. exports -1-in. coke, made from a local gas coal, to a ferro-silicon industry in Norway at a cost in excess of \$100/ton. The +1-in. coke is sold now as a domestic fuel at about \$167/ton.⁹⁴

Marketing Strategy

The U.S. coking and blast furnace iron industry would be strengthened in many respects by the development of a supplementary form coke process using nonmetallurgical grade coals. A continuous, enclosed production process, in contrast to the standard slot-type batch-operated coke oven, would be better able to meet environmental restrictions.

The issues of greater steel industry productivity, assurance of a secure domestic steel industry, a better U.S. trade balance position, reduced external pressures from the declining U.S. dollar, and increased employment opportunities will favor the development of economical coking processes. Market penetration could begin by extending current supplies of metallurgical coke by displacing coke imports. Expansion could occur in replacement for coke production from aging and environmentally unacceptable domestic facilities. In addition, the cost competitive nature of form coke and its acceptability by the metallurgical industries may even open up potentially significant exports to Europe.

Smokeless Domestic Fuel or District Heating Fuel

A third solid co-product option assessed is for the production of a smokeless domestic fuel. The product would be similar to form coke but it would be adjusted in composition to achieve acceptability as a substitute for anthracite coal or cordwood. The feedstock for the smokeless fuel would come from the integration of the mild gasification process with existing coal preparation plants. A portion of the clean coal product would be utilized to produce the smokeless fuel, while the remaining clean coal would be sold as a beneficiated steam coal. Beneficiation would occur because the fine portion would have been removed and used in the mild gasification process. In addition, excess heat produced in the gasification process could be utilized

to dry the steam coal. The reduction of fines and drying will increase the market acceptability and value of the coal.

The market price for the smokeless fuel can be determined from the relative prices for other similar domestic fuels, namely, anthracite and cordwood for domestic heating purposes. The cost of anthracite ranges from about \$65 to \$125/ton delivered for a residential size and grade (costs depend on distance from mines and retailing practices). Commercial grades of anthracite cost \$40 to \$50/ton. However, U.S. anthracite use peaked in 1970 at 100 million tons. About 3.2 million tons were produced in 1979 and about 3 million to 4 million tons were produced in 1986 of which about 75% was exported. In 1986, residential anthracite use was only 1 million tons. The balance was exported to Canada, Europe, and Korea in 1986.

When compared by heating value, the current domestic use of firewood would be equivalent to about 50 million tons of smokeless fuel. Cordwood generally costs about \$7 to \$10 per million Btu delivered in the United States.

While the acceptability of smokeless domestic fuel may face problems in the United States, the export market could be significant. Countries with a shortage of firewood or fossil fuels are candidate markets. Environmentally-concerned countries could use a smokeless fuel as a district heating fuel in better-controlled central boilers. In addition the smokeless fuel should also be useful for light industrial use.

A competitive export price of smokeless fuels would currently be about \$4.50/million Btu. This equates to about \$100/ton, which if delivered to Korea, includes \$30/ton for land and sea shipment. In comparison, as stated earlier, the Rexco process is now selling smokeless domestic fuel in the U.K. at a cost of about \$167/ton.⁹⁴ Smokeless fuel briquettes made from mild gasification char containing limestone to capture sulfur will provide the added benefit of significantly reducing sulfur emission upon combustion. These briquettes will have a heating value of about 10,000 Btu/lb with 30% ash. The Sulfur-tain process development work conducted with preparation plant wastes and a high sulfur Ohio coal at the Coal Research Bureau of West Virginia University has shown that briquetted coal with a Ca/S stoichiometric ratio of 2 could be burned with nearly complete SO₂ capture.⁹⁵ Smokeless briquettes made in Korea, for example, with Korean coal, U.S. anthracite, and

a clay binder, have a lower heating value, 8000 Btu/lb, and a higher ash content of 40%.

A comparison of the prices of conventional domestic fuels is illustrated in Figure I-78. The smokeless fuel is arbitrarily assigned a price of \$4.25 to \$4.50 per million Btu in order to make it competitive with widely used wood fuel.

A U.S. Rexco representative reported on a project to replace wood burning in a Colorado town with the smokeless fuel now manufactured in the U.K., in order to demonstrate a resulting improvement in air quality.⁹⁶ It is anticipated that this project will be conducted sometime this year. The results to be obtained from this demonstration project should be useful in determining the public acceptance of this new fuel form in the U.S.

Successful production and marketing of smokeless domestic fuel may provide another quality fuel that the U.S. could export to nearby Central and South American countries. This strategy is consistent with the policy of DOE to export clean coal products to the developing countries.⁹⁷ Using smokeless fuel from coal will aid the developing countries to slow down the ravages of deforestation.

Adsorbent Carbon or Char

The final solid co-product considered is an adsorbent carbon or char product that could be made by steam activation of the mild gasification char. A powdered form and/or a granular form could be produced. The present prices are about \$0.50 to \$1.00/lb in bulk for the powdered and granular activated carbon forms, respectively.

Adsorbent carbons are now made from a variety of carbonaceous materials including coal. Process steps include sizing, carbonizing, and activating. The powdered forms are generally mixed directly with a contaminated liquid stream for purification, whereas the granules are used in a packed bed through which the contaminated liquid stream passes. Treatment of effluent streams in the paper and pulp industry and treatment of refinery activated sludges are major uses.

COMPARISON OF DOMESTIC FUELS

A88040203S

Figure I-78. COMPARISON OF DOMESTIC FUEL PRICES

The U.S. demand for adsorbent carbons is presented below:

1980	125 X 10 ⁶ lbs/yr (62,500 tons/yr)
1986	200 X 10 ⁶ lbs/yr (100,000 tons/yr)
1990 (est.)	300 X 10 ⁶ lbs/yr (150,000 tons/yr)

The existing U.S. plant capacity is now about 300 to 330 million lbs/yr (150,000 to 165,000 tons/yr).

Demand will increase if rising concern forces enforcement of clean drinking water standards. However, compatibility of a coal-derived char (potential for leachable organics) with drinking water treatment would have to be demonstrated. Future demand may also be affected by the advent of natural gas-fueled vehicles using adsorbent carbon to store natural gas on board. This market could approach 450 million lbs/yr of adsorbent carbon if each of the 3 million vehicles (city trucks and buses and fleet vehicles) uses about 150 lbs/vehicle/yr. However, the possible production of char for upgrading to adsorbent carbon from one mild gasification plant processing 1 million tons/yr of coal would be about 1180 million lbs/yr, or 590,000 tons/yr of char, which is far in excess of the projected demand. The market for adsorbent char may be too small for a single, devoted solid product from the mild gasification process. However, this market could be considered if a dual solid product option could be implemented within the mild gasification process. Diverting a portion of the char stream to adsorbent char or low-sulfur char preparation from the main char product, such as form coke or domestic fuel, may be feasible.

Market Assessment of Condensable Hydrocarbons

The markets for the coal-derived condensable hydrocarbons is small compared to the coal utility market. In addition, the petroleum-derived equivalents dominate the market and, with the existing soft oil prices, the current market preference for coal-derived products is limited. Since the low-temperature tar is closer to crude oil than the high-temperature coke oven tar, many were promoting mild gasification oils and tars as substitute liquid fuels. However, because of the aromatic nature, high ash, high sulfur, higher oxygen content, and lower heating value, the coal liquids will have to be filtered and may require severe hydrotreatment to adequately reduce the contaminants. Even though recent claims advocate the direct use of the coal

derived liquids along with diesel fuel, there is not any existing experience with the extended performance of internal combustion engines with these fuels. Besides, even if the market does exist for these liquid fuels, they could only be sold at a price comparable to No. 6 fuel oil of about 35¢ to 45¢/gal, which is not considered to be a value-added price. At this cost, it may be difficult to justify any separation and upgrading of the coal-derived condensables.

The Koppers Co. and Reilly Tar and Chemicals are the two largest coal tar processors in the U.S., and they will purchase the crude condensable hydrocarbons (with less than 2% moisture) at a price of 40¢ to 46¢/gal, which is higher than the fuel value.^{98,99} In order to explore other potential value-added uses, further discussions were held with Allied Signal, USX, Western Tar, Coopers Creek, and Carbochem of Canada.

The important information required to identify the value-added uses for the major constituents of the coal-derived condensable hydrocarbons were obtained from Koppers and Reilly Tar and Chemicals. A discussion of the key condensable co-products is given below.

Tar Pitch

Pitch is derived by the fractionation of the condensable hydrocarbons produced during mild gasification. Depending upon the processing conditions, the pitch fraction can be from 25% to 55% of the coal tar. Pitch can be used as a binder for electrode manufacture for the steel and aluminum industries. Pitch is also useful as a roofing or road tar and as a special protective coating and sealant. Koppers has stated very clearly that coal tar pitch drives their business. About 95% of the pitch market is controlled by Koppers and by Reilly Tar and Chemicals.

The price for pitch as an electrode binder is about \$250/ton and about \$150/ton for roofing and road tars. Most of the pitch from coke oven operations is used as an electrode binder, because of its high C/H atomic ratio, making it preferable to petroleum pitch.

The U.S. production of pitch from coal has been declining as a result of the declining U.S. production of metallurgical coke. Figure I-79 shows the U.S. coal tar production data from 1965 to 1984.¹⁰⁰ In 1985, the United States produced about 1200 million pounds of pitch. About 185 million pounds were imported from Canada, Mexico, Asia, West Germany, and Australia.

Figure I-79. COAL TAR PRODUCTION TRENDS IN THE UNITED STATES
FROM 1965 TO 1984¹⁰⁰

The future of U.S. pitch production and pricing is tied to the U.S. coke production and the marketing of petroleum products, namely petroleum pitch. However, coal-derived pitch is now in very strong demand by the domestic and foreign aluminum industry, and also by the metals industry in general, to produce electrodes and graphite blocks for cupolas.

The production of graphite products from pitch coke is expected to increase due to a growth in world demand for electrodes in electric arc steelmaking and aluminum ore reduction. Graphite is also made (bound with pitch) into furnace liners in the metal industries. The production of graphite products was 154,500 tons in 1983 (down from 286,000 tons in 1979), but as electric arc steelmaking increases, this will increase. The current price of pitch coke is about \$340/ton.

Pitch produced in the United States would curtail the imports from China, Japan, Korea, and Germany and contribute to a reduction in the national trade deficit.

Heavy Creosote Oil

The heavy oil fraction from coal, represented by creosote oil, is used mainly as a wood preservative and to produce carbon black for the rubber industry. Carbon black is produced by incomplete combustion of creosote oil. The use of creosote oil as a wood preservative is declining due to environmental concerns. The present price of creosote oil is \$1.00/gal, as reported by Koppers Co. In 1986 the U.S. production of creosote oil was 80 million gallons. Imports of creosote oil in 1985 were 11.5 million gallons mainly from the Netherlands, West Germany, and France.

Carbon Black

The prices for carbon black from a variety of feedstocks vary from \$0.26 to \$0.32/lb. About 90% of carbon black produced, is used by the rubber industry not only for the coloring, but for the improved physical structure and resistance to oxidation resulting from the compounding of carbon black with rubber. The balance of carbon black produced is used by the pigment and ink industry.

Presently, the bulk of carbon black is produced from heavy petroleum liquids, which control the price. The heavier coal-derived liquids can also be used, and in some cases are superior to petroleum feedstocks, for carbon

black production. The U.S. production of carbon black from all sources is reported as 1.45 and 1.29 million tons in 1984 and 1985, respectively.

Middle Oils

The major extractable components of middle oil from coal are phenol and naphthalene. Recent prices for phenol are \$0.34/lb and \$0.22 to \$0.30/lb for naphthalene. Production figures for naphthalene were difficult to obtain. Most of the naphthalene produced from coal tar liquids is converted to phthalic anhydride, which is used as a plasticizer.

The supply and price components of these are dominated by petroleum refining. Phenol demand may increase because of its increasing industrial use in manufacturing fireproof phenolic foam insulation. U.S. production of phenol, phthalic anhydride, and BTX are given in Table I-39.^{101,102}

Table I-39. U.S. PRODUCTION OF SELECTED CO-PRODUCTS^{101,102}

	<u>1982</u>	<u>1984</u>	<u>1985</u>	<u>1986</u>	<u>1987</u>	<u>1988 (est.)</u>
Phenol, 10 ⁶ tons	NA	2.750	2.841	3.115	3.300	3.450
Phthalic Anhydride, 10 ⁶ tons	NA	0.43	0.41	NA	NA	NA
Benzene, 10 ⁶ gals	1052	1318	1283	1362	1520	1600
Toluene, 10 ⁶ gals	714	728	688	760	775	790
o-xylene, 10 ⁶ lbs	802	688	697	788	950	1000
p-xylene, 10 ⁶ lbs	3391	4264	4779	5035	5300	5600

NA -- not available in sources used.

Light Oils

The major extractable components of the light oil fraction from coal are benzene, toluene, and xylene. Recent prices for these products have been \$0.95/gal for benzene, \$0.77/gal for toluene, and \$0.78/gal for xylene. The market is again dominated by petroleum refiners. The uses of these chemicals are many as a chemical feedstock. They also can be used as additive octane enhancers for gasoline.

Ammonium Sulfate

Ammonium sulfate is a minor product stream that can be obtained from the ammonia produced during mild gasification and it can be easily sold to the fertilizer industry. Prices for commercial grades of ammonium sulfate have been about \$60 to \$80/ton.

Marketing Strategy

Based on the information obtained from the major coal tar processors, it is evident that the nonfuel uses for the condensable co-products will generate sufficient additional revenues to improve the economics of conceptual commercial mild gasification processes. Of the markets surveyed, the value added uses for the major components in the condensable fraction are as follows:

- Pitch for electrode binders and graphite blocks
- Heavy creosote oil for carbon black production
- Middle oil to produce phenols and naphthalene
- Light oils to produce BTX for chemical feedstocks and as an octane enhancer.

The expected annual yield of these chemicals from one integrated mild gasification plant is shown in Table I-40. The comparison of the annual co-product yields to the most recent U.S. annual production is also given, including the two formed solid products.

Table I-40. COMPARISON OF CONDENSABLE HYDROCARBON YIELDS FROM ONE INTEGRATED MILD GASIFICATION PLANT WITH MOST RECENT U.S. PRODUCTION

<u>Co-products</u>	<u>Annual Mild Gasification Yields</u>	<u>Percent of U.S. Production</u>
BTX	8-11 X 10 ⁶ gals	0.3
Phenols, etc.	16-17 X 10 ⁶ gals	2.0
Pitch	36-53 X 10 ⁶ lbs	4.0
Pitch Coke	24-36 X 10 ⁶ lbs	NA
Creosote	19-20 X 10 ⁶ gals	25.0
Smokeless Fuel	1.0 X 10 ⁶ tons	2.0
Form Coke	0.8 X 10 ⁶ tons	3.2

* 1.4 million tons/year integrated plant capacity.

While the demand for these co-products is very strong at present, the anticipated growth in demand is modest at best. However, there are two critical factors which could quickly improve the demand. These include a disruption in the OPEC oil supply and a worldwide economic recovery which would put a lot of pressure on the metals and chemical industry to expand rapidly.

The market survey has identified aromatic products as being the preferable mild gasification co-products. Consequently, the reactor development effort will be directed to maximize the production of aromatic condensables.

Conclusions From Market Assessment of Solid and Condensable Co-products

The market assessment showed that the value-added solid products from the mild gasification process would be char/coal blend utility fuel, form coke, smokeless fuel, and adsorbent char. Other products or applications identified, as discussed in Appendix C, need additional product development for advanced or specific technology applications.

The market assessment information was developed by IGT in consultation with Peabody Holding Co., Bechtel National, Inc., and representatives of utilities, the iron and steel industry, and other industries. Information was gathered on the expected demand, pricing levels, commercial product acceptance, and near-term market directions.

Form coke and smokeless fuel show the greatest present market potential. The future demand for adsorbent chars may be larger if clean drinking water standards are enforced and natural gas fleet vehicles become prominent in cities. However, that market by itself may be too small for the single, devoted product of mild gasification. A dual solid product option may be feasible to supply the adsorbent char market.

A key factor resulting from these discussions is that for any of the solid product options, the integration of the mild gasification process with a coal preparation plant leads to synergistic benefits. The main benefits of the integration are that the delivered steam coal product to the utility will be drier with less fines, and the fines from the preparation plant will be utilized in the mild gasification process, thus aiding the throughput and productivity of the coal preparation plant.

The market survey and assessment of the potential condensable hydrocarbons from the mild gasification process identified the following products that would qualify as value-added products: pitch, creosote oil, phenols, naphthalene, and a mixed stream of benzene, toluene, and xylenes (BTX). The use of any of the condensable hydrocarbons as fuels would not be a profitable value-added situation in the present energy market, without considering the expected upgrading processing required.

Discussions with the Koppers Co. and Reilly Tar and Chemicals Co. and other tar processors provided information about the markets and prices for coal tar-derived products. Computerized marketing data bases were utilized to develop production, import, and forecast information. While the present demand for these products is good, the future demand is expected to grow slowly. Oil price increases or a reduction in availability would increase the demand for coal-derived products as would a general worldwide economic upturn. At present the coal tar liquids are produced exclusively from metallurgical coal coking ovens. The number of U.S. coke ovens are declining mainly due to age and new units are very costly to build to satisfy environmental concerns. Meanwhile, imports of coke and coal tar liquids may increase dramatically and thus adversely affect the market. Hence, the development of a mild gasification process, which provides for better control of all process streams could revive the U.S. coal tar industry and regain or even open new opportunities for the U.S. coal industry.

DISCUSSION OF MILD GASIFICATION TECHNOLOGY

Mild Gasification Reactor Systems

A wide variety of reactors have been employed to carbonize coals ranging from lignites to bituminous coals. The preferred process conditions for mild gasification dictates the reactor design. The gas-solid contacting method defines several of the process parameters, particularly particle size and particle heat-up rate. The following information is a brief summary of the advantages and disadvantages of the major types of reactors given in Table I-41, and is discussed below.

Fixed-Bed Reactor

The major advantage of the fixed-bed reactor is its simplicity and the fact that it has been extensively developed. Most of the reactors have been based on coke-oven designs adapted to low-temperature carbonization. The basic technology is simple and any coal of any particle size can be used since the char mass must be pushed out or dislodged by some mechanical means following carbonization.

There are several disadvantages of fixed-bed carbonization reactors: It is a batch operation which is slow and difficult to scale up; throughput is limited; environmental controls are difficult because of the necessity of opening the vessel to remove the char; there is little flexibility or control over the product slate due to the nonuniformity of reactor conditions; and the method is limited to slow particle heating rates. Internal heating has been used to minimize the latter two of these effects, but in this case, the feed properties are severely limited due to flow patterns and pressure drop.

Vertical Moving-Bed Reactor

The vertical moving bed offers advantages over the fixed-bed in that it can be operated continuously and it is more practical to incorporate in it the design modifications such as internal heating and the injection of various gases or steam. Volatiles can be withdrawn continuously from the reactor. Increased throughput and better control over product quality are the consequences of these advantages.

The principal disadvantage of the vertical moving-bed design is the difficulty associated with movement of the coal through the reactor. Any

Table I-41. COMPARISON OF CONCEPTUAL MILD GASIFICATION REACTOR TYPES

Reactor Type	Coal Type	Gas-Solid Contacting	Method of Heating	Pressure Drop	Conversion	Scale-Up Capabilities	Additional Remarks
Fixed-Bed Batch Reactor	All types of coals, single screening adequate for non-caking coals.	Non-Uniform and hence requires long residence time	Slow, indirect heating, non-uniform because of batch operation	Low gas velocity and may present a problem with caking coals	High char and gas yields due to cracking of condensibles,	Limited coal throughput difficult to scale-up	Can handle lump size coal, requires mechanical dislodging of char, caking coals may require double screening to remove fines, unsuitable for introducing reactive gases
Vertical Moving Bed Reactor	Can handle only non-caking coals, requires double screening	Uniform for uniformly sized particles, long residence time	Slow, direct heating is possible, operates with a thermal gradient	Low-gas velocity with low pressure drop	High char and gas yields due to cracking of condensibles	Low coal throughput, and limited scale-up capability	Can handle lump size coal, continuous operation, low condensible hydrocarbons yield, low in aromatics content, little or no char entrainment
Horizontal Moving Bed and Conveyor Bed Reactor	All types of coals, caking coals may present problems, requires double screening	Uniform for uniformly sized particles, long residence time	Slow, direct heating is possible	Low-gas velocity with low pressure drop	High char and gas yields due to cracking of condensibles	Limited coal throughput and difficult to scale-up	Can handle lump size coal, requires mechanical movable parts exposed to reaction conditions, low yield of condensible hydrocarbons, low in aromatics content, little or no char entrainment
Fluidized Bed Reactor	All types of coals, single screening adequate, caking coals can be processed	Uniform and rapid mixing, short residence time, back mixed solids may require careful design of char withdrawal	Rapid heating with nearly uniform temperature	Higher than fixed and moving bed reactors	Will reduce secondary cracking of condensibles thus increasing their yield	High coal throughput, can be scaled-up to sizes approaching commercial cat-crackers	Particles >1/4 inch are difficult to fluidize, continuous operation, high condensible hydrocarbons yield with high aromatics content, some char carryover due to attrition and requires cyclone separation of fine char particles
Entrained Bed Reactor	All types of coals, fine size coals are well suited, caking coals can be processed	Uniform and very rapid mixing, very short residence time	Rapid heating with uniform temperature	Low for fine coal particles	Will keep secondary condensibles cracking reactions to a minimum	Very high coal throughput, scale up limited to commercial riser crackers	Particles should be below 100 mesh, continuous operation, may result in very high char carryover with the condensible hydrocarbons, high yield of condensible hydrocarbons with high aromatics content, possible erosion of reactor internals

agglomeration or sticking that obstructs the movement of coal is a serious problem. For this reason, severely caking coals have generally not been processed in this type of reactor, and even slightly caking coals require some form of pretreatment or mechanical stirring. For other coals, the feed has generally been restricted to briquettes or lump coal. In addition, the particle heating rate, though more uniform than in fixed beds, is too slow for optimum mild gasification.

Horizontal Moving-Bed Reactor

The horizontal reactor design offers the same advantages as the vertical moving bed compared to the fixed-bed design. In addition, the horizontal design avoids some of the problems associated with moving the coal particles by gravity alone. Most of the horizontal designs use some mechanical means to move the coal through the reactor, either by rotation of the reactor vessel or by some internal paddles or screws.

The disadvantages of this design, in addition to those mentioned for vertical moving beds, include the added complexity of moving parts. As with vertical moving beds, there are limitations in the ability to process caking coals. Because of size limitations imposed by the mechanical features, the throughput rate is limited.

Conveyor-Bed Reactor

Conveyor-type reactors are essentially similar to horizontal moving beds, except for the difference that the moving element is a flat pan or similar device. The technology of conveyor equipment is well established, and distribution of the coal in a thin layer on the conveyor allows more flexibility in coal particle size range.

The disadvantages of this type of reactor include very limited throughput and the difficulties associated with the exposure of moving parts to the high temperature and potentially corrosive environment inside the reactor vessel.

Fluidized-Bed Reactor

The fluidized-bed design offers numerous advantages over fixed-bed or moving-bed designs. Mass and heat transfer are much more rapid, resulting in a greater uniformity in processing conditions, and thus greater control over the product characteristics. Particle heat-up rates are much higher,

resulting in potentially higher condensable yields. The residence time of volatiles is also limited since the fluidizing medium moves at a relatively high velocity through the bed. The design is relatively simple, and allows for easy scale-up. Throughput can be greater than with other reactor configurations. Additionally, solid diluents, additives, or catalysts can easily be introduced into the reactor since mixing in a properly designed fluidized bed is uniform.

The chief disadvantage of coal pyrolysis in a fluidized bed is the difficulty of processing caking coal; agglomeration upsets the properties of the fluidized bed. Pretreatment of caking coals by partial oxidation has been used as a method of overcoming this in coal gasification. In other designs, such as KRW and U-GAS processes, the maintenance of a certain amount of char inventory in the bed has been proven sufficient to avoid excessive caking. The addition of other particulate solids such as sulfur-capture additives can also prevent agglomeration.

Entrained-Bed Reactor

The advantages of entrained-bed reactors are similar to those of fluidized beds. In addition, the entrained-bed design allows for even higher particle heating rates, shorter residence times, and higher throughputs. Solid-solid contact is more limited than in fluidized beds. These factors can result in the highest tar yields attainable in a continuous mild gasification reactor.

There is a limitation in the particle size range which can be processed in an entrained bed, based on the hydrodynamics of the particle-fluid system; the particles must be small enough to be entrained in the gas phase at a practical gas velocity.

Selection of a Reactor Design

A review and comparison of the published fundamental mild coal gasification research data with the large-scale process performance data, points out that the significant benefits of mild gasification are yet to be realized in commercial operations. The state-of-the-art mild gasification technology involves processing noncaking, low-rank, and low-sulfur coals at slow heat-up rates, with the endothermic energy being supplied by partial combustion of the valuable devolatilization products, very often within the reactor system.

The discussion in the previous sections clearly shows that these practices are not favorable for producing the value-added coal-derived products. The knowledge gained from the advanced coal gasification process research-and-development experience during the past two decades forms the basis for proposing a reactor system with several improvements over the available technology. The process development research for KRW and U-GAS (and other fluidized-bed systems) have clearly shown that highly caking bituminous coals could be directly gasified in a single-stage fluidized-bed reactor. In fluidized beds the agglomeration of caking coals may be controlled by the rapid distribution of the fresh feed coal throughout the bed of nonplastic, almost completely devolatilized char. By properly designing a coal feed system, operating with a predetermined char inventory in the reactor, maintaining a high superficial gas velocity in the reactor, and by designing a turbulent fluidizing gas distributor, it is possible to process caking coals in large reactors, at specific throughput rates of up to 1000 lb/ft²-h. If a single vessel mild gasifier can be developed, it will be simpler in design compared to the staged heating employed to process caking coals in the COED process. Rapid coal particle heat-up rate up to 10⁴°C/s is possible in fluidized-bed reactors, and it is possible to achieve higher heat-up rates of up to 10⁵°C/s in entrained-bed reactors. The fluidizing and/or the entraining medium could be made up of hot flue gases, recycled fuel gas, steam, CO₂-rich gaseous steam, or their mixtures. Alternatively, the heat of reaction could be supplied by recirculating hot char, which will also aid in reducing the agglomerating tendency of caking coals. The ability to process caking coals in a controlled gaseous environment, under rapid particle heat-up rate conditions is clearly the preferred approach to improve the yield of condensable hydrocarbons rich in aromatics, which will derive the value-added benefits for the mild gasification co-products. This was established by the literature surveys and the market assessment study.

The published literature on the use of Eastern bituminous coals was reviewed to identify large-scale continuous devolatilization test data, where the endothermic energy was supplied either by high-temperature gases or by hot circulating char or inert solids. It was also necessary that the test coal and the resulting condensables were adequately characterized. The Occidental Research Company entrained devolatilization tests conducted with western Kentucky No. 9 coal were found to be the most appropriate, although the

detailed characterization of the condensable hydrocarbons was not reported.⁶ The devolatilization results from Test No. 174 were selected as the basis for estimating the selected reactor performance. A summary of the Occidental's Test No. 174 results is given in Figure I-80. The information available on the condensable fraction was supplemented by the detailed product distribution reported for the Coalite process in the U.K.¹⁰⁴

For reactor scale-up purposes, it is desirable to use the specific throughput rate parameter expressed as $\text{lb/ft}^3\text{-h}$; however, such information is not available for devolatilization or carbonization of bituminous coals in a single-stage fluidized bed reactor. Consequently, the specific throughput rates, expressed as $\text{lb/ft}^2\text{-h}$ for the advanced coal gasification and coal carbonization processes, were reviewed. The information available on coal gasification processes, both at IGT and elsewhere,^{105,106} shows that, at pressures ranging up to 1000 psig and temperatures up to 1850°F, the specific throughput varies from about 500 to 1600 $\text{lb/ft}^2\text{-h}$. These processes require coal residence times up to 1 hour to achieve total carbon conversion to fuel gases. Most of the fluidized-bed carbonization research was conducted with laboratory-scale reactors, up to 6-inches in diameter.⁸ The COED process employs staged heating in four fluidized beds. The largest operating fluidized-bed carbonizer in the U.S. is the FMC plant at Kemmerer, Wyoming, which is designed based on the experience derived from the COED process. At this plant about 115,000 tons-per-year of subbituminous coal is carbonized at about 900°F to produce char for form-coke in a 13-ft-ID reactor.¹⁰⁷ The estimated throughput rate for this carbonizer is slightly higher than 200 $\text{lb/ft}^2\text{-h}$. The operating temperature for the selected mild gasification reactor is 1200°F, 300°F higher than the FMC carbonizer, and unlike coal gasification reactors, the mild gasification process will primarily achieve devolatilization with about 30% carbon conversion. The kinetics of devolatilization¹⁰⁸ are very rapid, and it is estimated that devolatilization is essentially complete in a few seconds. Considering all of this information, it was decided to use 500 $\text{lb/ft}^2\text{-h}$ specific throughput rate as the basis for estimating the fluidized bed reactor diameter.

The reactor concept proposed for testing, refinement, and development during Task 2 features an integrated fluidized- and entrained-bed reactor with independent coal feed systems for the two reactor stages. The primary reasons

Figure I-80. PROJECTED MILD GASIFICATION REACTOR PERFORMANCE

for selecting a combination of contacting methods are to provide the flexibility for product selectivity by varying the feed distribution between the two stages, and also to provide the option to utilize the significant fine coal (for example, -28 mesh) material available in coal preparation plants. In the first instance, varying the coal heat-up rate and residence time have been shown earlier to affect the product composition and yields. The utilization of preparation plant fines in the entrained stage of the mild gasifier facilitates better integration with the existing coal preparation plants. For preliminary technical evaluation purposes, one-third of the feed coal is fed to the entrained-bed stage while the rest is converted in the fluidized-bed stage.

For the conceptual 10^6 tons/yr plant, three mild gasification reactor trains, each with 3000 tons/day dry coal capacity, were selected. A single gasifier processing two-thirds (667 tons/day) of the total coal feed in the fluidized-bed stage reactor at about 500 lb/ft²-h would require a 12-ft-ID vessel. Reactor redundancy will provide advantages in operational continuity; thus the size was selected to allow less expensive shop fabrication rather than field fabrication techniques.

In the preliminary design, to maximize the co-products yield, the energy for mild gasification will be supplied by a high-temperature gaseous stream with little or no residual oxygen. Because the sensible heat required to raise the temperature of the coal particle to the reaction temperature is an order of magnitude higher than the heat of carbonization, it is desirable to dry the coal first and also to preheat it to the highest possible temperature, without exceeding the threshold temperature for devolatilization. For this purpose 450°F (232°C) was selected as the temperature to which the coal would be dried and preheated before it is fed to the mild gasification reactor. Considering that the endothermic energy for mild gasification is supplied primarily by the gases generated by combustion of a part of the product fuel gas, the estimated flue gas composition is:

	<u>% by Vol</u>
CO ₂	12.7
H ₂ O	17.3
N ₂	<u>70.0</u>
Total	100.0

Using calculated molar specific heats for the flue gas of 9.05 Btu/lb-mol °R at 1200°F and 10.24 Btu/lb-mol °R at the reactor distributor temperature of 2000°F, the estimated flue gases required to devolatilize 1000 tons/day of coal from 450° to 1200°F is estimated to be 2948 lb-mol/h. During mild gasification, approximately 30×10^6 Btu/h is transferred from the flue gases to the 41.67 tons/h of preheated feed coal. For these calculations, the specific heat of coal is taken as 0.45 Btu/lb °F, and the heat of devolatilization is considered to be negligible.

In order to maintain a high degree of turbulence and good gas-solids mixing in the coal feed region, the superficial gas velocity will be maintained at about 6 ft/s, where the feed coal comes in contact with the hot flue gases. The fluidized-bed stage will have a dual diameter to provide rapid mixing as the feed coal passes through the plastic range.

The entrained stage located above the fluidized-bed reactor will process the remaining one-third of the gasifier feed coal, or about 223 tons/day. The coal, preheated to about 450°F, will be carbonized to 1200°F in entrained mode by contacting with about 973 lb-mol/h of 2000°F flue gases. The entrained stage will be 6 ft in diameter to maintain a superficial gas velocity of 20 ft/s. The entraining gases will be made up of 973 lb-mol/h of 2000°F flue gases and all the gases from the fluidized-bed stage underneath. The estimated throughput rate of about 980 lb/ft²-h in the entrained stage is comparable to values reported in U.S.B.M. investigations.¹⁰⁹ Figure I-81 shows the major dimensions of the conceptual integrated fluidized- and entrained-bed reactor and the calculated superficial gas velocity in selected locations.

Other variations on the integrated reactor design were examined. A swirl reactor is one such variation, in which a swirling dense turbulent bed of char fines is held in a flattened cyclonic contactor. The gas and char fines discharge downward through an orifice. The backmixed swirling solids provide enhanced solids residence times and, by dilution of the fresh feed with spent char, discourages agglomeration of the coal fines feed in a similar manner as the backmixed fluidized bed does for the coarser particles. The swirl reactor, along with other conceptual fine coal gasification schemes, will be reevaluated in the process engineering studies associated with the optional project tasks before finalizing a demonstration plant reactor design.

Figure I-81. SCHEMATIC DRAWING OF PROPOSED MILD GASIFICATION REACTOR

The process scheme described thus far relies primarily on utilizing the sensible heat from waste gas combustion flue gases for the mild gasification of coal. The technology development investigations in the optional Task 2 and Task 3 may establish the basis for selecting the mild gasification medium from the alternatives to the flue gas, including recycled fuel gas, steam, CO₂-rich gaseous stream, hot char recycle, or some combination of one or more of these streams.

An illustrative concept for the integration of the mild gasification into a commercial application is given in Figure I-82. In this design concept the heat required for the mild gasification is derived by combustion of a portion of the char fines produced in the entrained bed contactor. The net production of intermediate-Btu-content fuel gas is treated for sulfur removal in a moving-bed hot-lime process. After cooling (via heat recovery) as required for efficient compression, the fuel gas provides fuel for combined cycle cogeneration of electrical power.

The detailed reactor design will be prepared during the optional Task 4 investigation, for which the process development unit results of the Task 2. Study will be essential. The detailed reactor design will include the basis for selecting the operating conditions, address the merits of the integrated reactor system, feed specifications for the two reaction stages, gasifier dimensions, number of feed points, char withdrawal system, the provision for introducing, and separating if needed, sulfur-capture additive, distributor design, and the selection of a fluidizing medium and its properties. The materials of construction for the gasifier will be carbon steel with adequate refractory lining to handle the mild operating conditions. Detailed specifications for materials and instrumentation will be provided during Task 4 investigations.

Conceptual Advanced Mild Gasification Process Schemes

The identification of the value-added uses for the mild gasification co-products, as described under the market assessment study, and the method of their production from coal, suggested by the literature surveys, formed the basis for the integrated coal preparation mild gasification concepts described below. Three options are described differing in their provision for utilization of the product char. The co-products resulting from these options are considered to open new markets for coal in the next 5 to 10 years. The

A88060248P

Figure I-82. ILLUSTRATIVE INTEGRATED PROCESS

indicated liquids recovery scheme, however, is illustrative only and patterned after that in common use for recovery-type coke oven batteries. The possibility for elevated pressure operation, together with advances in shale and coal pyrolysis recovery trains, suggests that a more optimum scheme may ultimately be proposed. This could impact the distribution of individual liquid products, but not their overall composition and quantity. A description of the illustrative process schemes and an approximation of their revenue potential are given in Options I, II, and III. The three schemes all employ the same condensable co-product recovery concepts conventionally used for recovery-type low-sulfur coal coking systems. Alternative arrangements may be found that are preferable for the unique requirements of mild gasification of high-sulfur coal.

Option I. Char/Coal Blending for Utility Fuel

The conceptual mild gasification process consists of 16 steps, each of which is comprised of several unit operations and unit processes. Figure I-83 shows the conceptual process flow diagram for Option I. The stream flow rates are based on a dry basis coal feed to three mild gasification reactors of equal capacity totalling 3000 tons/day. All input and output stream flows are given in tons/day on a dry coal basis. The principal process steps are.

Size Reduction

Run-of-mine coal (11,428 tons/day) is crushed and screened to yield a 6-in. X 0-in. raw coal feed. Based on Peabody preparation plant experience, this product contains up to 37.5% under 1/4-in. which is considered an under-size fraction. The entirety of the sized coal is sent to the coal cleaning step.

Coal Cleaning

The raw coal feed from the size reduction step is subjected to conventional coal washing to reduce ash and sulfur content. During washing the coal is further split into a coarse (6-in. X 1-in.), middling (1-in. X 1 mm), and fine (1 mm X 100 mesh) streams which are each treated to a different washing scheme. During washing, coarse refuse (gob) and the -100 mesh stream are rejected and are expected to total about 3428 tons/day.

Dewatering/Screening

The coarse coal fraction is screened and crushed to a top size of 2-in. The middling and fine streams are fed to mechanical dewatering devices where surface and interstitial water are removed. At this point, a screening operation would be incorporated into the process that would yield a coarse product (2-in. X 1/2-in.), a middling product (1/2-in. X 1/4-in.), and a fine product (1/4-in. X 0-in.) stream. The fine product stream, approximately 3000 tons/day would be fed to the dryer/preheater as preparation for mild gasification. The middling fraction, amounting to about 1800 tons/day, would be sent to the char/coal blending step. The char/coal blend will be further blended with the coarse product, approximately 3200 tons/day producing a total of 6812 tons/day of char/coal blend utility fuel.

Dryer/Preheater

The 1/4-in. X 0-in. cut from the dewatering/screening step is dried to about 5% to 10% moisture and preheated to approximately 450°F by exposure to hot flue gases from the in-plant combustor, which produces heat from the combustion of product fuel gases (or alternatively char fines). The 3000 tons/day (dry basis) output from this step is delivered directly to the mild gasification reactors.

Mild Gasification

The mild gasification step consists of three gasifiers, each with 1000 tons/day capacity, as described in the section on selection of reactor design. The mild gasifiers operate at a temperature of 1200°F and a pressure between atmospheric and 50 psig. The fluidizing/entraining gas is a mixture of hot flue gases from the fuel gas combustor and (optionally) steam produced from waste heat recovery. The coal feed may include an optional solid phase sulfur-capture additive.

Two output streams exit the mild gasification step: the solids- and tar-laden gas; and the devolatilized char mixed with the partially sulfided additive, if that option has been utilized.

Solids Disengagement

The solids-laden off-gas from the mild gasification step exits the top of the reactors, and char fines are removed by one or more high-temperature

cyclones. The char fines are then blended back with the bottom char product. Alternatively they may be recycled to the retort to provide a portion of the required heat, or may be burned in place of fuel gas to provide the hot recycle gas stream.

Char Blending

The hot (1200°F) coal char exiting the mild gasification operation, totalling 1812 tons/day after char fines recovery, is blended with the 1/2-in. X 1/4-in. middling cut from the preparation plant dewatering/screening step. The sensible heat contained in the char is used to dry the coal fines; also, the blending of hot char and cold coal fines is performed in a controlled manner in order to increase the average particle size by the agglomeration of coal particles as the temperatures approach the plastic range. This should improve the shipping and handling characteristics of the resulting utility fuel product. The partially agglomerated char/coal mixture is then blended with the 2 in. X 1/2 in. fraction from the dewatering step to produce a solid fuel product with the desired properties.

As an option, part of the hot char is removed prior to the blending step for in-plant combustion to provide process heat.

If a solid additive such as lime has been used in the mild gasification step, the additive could remain with the char in order to provide the solid fuel mixture with sulfur-capture properties during char combustion in a subsequent step.

Spray Coolers

Gas cooling and recovery of condensables are achieved in this step by standard coal-tar quenching and recovery methods, as described previously. For simplicity, several operations are categorized together in the spray cooling process step. Recycled acidic quench liquor, saturated in ammonium sulfate and containing a 5% excess of sulfuric acid, is used in one or more spray quench coolers. The volatile product stream is ultimately cooled to about ambient temperature in this operation. The raw gas exiting this step, which is saturated at about 70°F with light oil, amounts to 393 tons/day.

A portion of the naphthalene produced in the mild gasifier will be condensed from the product gases in the final cooling stage, where it is skimmed from the aqueous layer or extracted with an oil wash.

Ammonium sulfate in crystalline form is recovered from the quench liquor in a crystallizer; this is made possible by the super-saturation of the quench liquor with ammonia from the product gases.

The condensate, consisting of an organic condensable phase and an aqueous liquor, is delivered to a decanting step for separation.

Decanter

The organic and aqueous phases of the condensate are separated by decanting, yielding 668 tons/day of raw tar and 127 tons/day of liquor. The aqueous liquor, containing ammonia, phenols, and other water-soluble organic compounds, is sent to the saturator which supplies quench liquor to the spray coolers. The organic condensables are sent to the tar distillation and fractionation step.

Saturator

In this process step, ammonia recovered from the decanted liquor by distillation is recombined with the incoming liquor and sulfuric acid to form the acidic saturated ammonium sulfate solution used as a quench liquor.

Ammonia Still/Extraction

The excess liquor from the saturator is treated with alkali or lime to release ammonia, which is steam-stripped from the liquor and recycled to the saturator. The waste liquor is then cooled and extracted with aromatic solvents to recover 1.2 tons/day of phenols, including approximately 0.4 tons/day of dihydric phenols (catechol, resorcinol, and their derivatives), which are then regenerated or "sprung" from the solvents by treatment with aqueous alkali. The waste liquor stream, exclusive of any added water from steam stripping or other auxiliary inputs, amounts to 126 tons/day.

Recirculating Oil Scrubber

Raw noncondensable gases exiting the condensation step are contacted with a suitable solvent which can be a fraction of the middle oil recovered from fractionation of the coal tar, or a petroleum-derived solvent. Light oils, including benzene, toluene, and xylenes (BTX), are absorbed from the product gas by this method. The "enriched" wash oil is sent to steam stripping to recover the light oils.

Steam Strippers

Steam distillation is used to remove the light oils from the wash oil. The light oil consists of approximately 52 tons/day of BTX, plus small amounts of indene and coal tar naphtha. The recovered light oils are combined with light oils fractionated from the condensable liquids in the tar fractionation step, and the lean wash oil is recycled back to the recirculating oil scrubber.

Tar Fractionation

In order to recover the high-value products from the raw organic condensables produced by mild gasification, a fractionation system is required. This process step involves primary distillation and steam stripping of light oils. The removal of tar acids by alkali treatment, recovery of tar bases by treatment with acid, and further fractionation of the major fractions to recover BTX, indene, tar naphtha, light phenols, cresylic acids, naphthalene, pyridine bases, and creosote oil cuts are options.

In primary distillation, the condensable product, following filtration, is flash-distilled to produce four fractions:

- Light oil, distilling up to 360°F (180°C), approx. 25 tons/day
- Middle oil, distilling up to 590°F (310°C), approx. 220 tons/day
- Heavy oil, distilling up to 750°F (400°C), approx. 287 tons/day
- Soft pitch, distillation residue, approx. 181 tons/day.

The input streams to the tar fractionation step are the raw organic condensable phase from the decanter and the oil recovered from the pitch cracking operation.

Pitch Cracking

In order to produce a hard pitch of premium value, suitable for electrode binder use, it is necessary to further process the soft pitch produced by the low-temperature mild gasification. A simple thermal treatment of 1450°F is used to crack the pitch to produce 36 tons/day of pitch coke suitable for use as graphite, 54 tons/day of hard pitch, 45 tons/day of oil which is recycled back to the tar fractionation step, and 45 tons/day medium-Btu fuel gas which is combined with the primary fuel gas recovered from the oil scrubber step.

Option II. Metallurgical Form Coke Production

In this option, char and pulverized coal are combined to manufacture metallurgical form coke. The coarse fraction from the dewatering/screening step in the coal preparation circuit is used for sale as a utility fuel.

All of the process steps except the form coking operation are similar to those described under Option I. The addition of a volatile stream from the form coke high-temperature carbonization step changes the yield and distribution of gaseous and condensable products from the overall process. This is reflected in the tons/day yields of the product streams as shown in Figure I-84.

Form Coking

In this step, the hot (1200°F) char from the mild gasifier and the solids disengagement step are combined and blended with cleaned, dewatered pulverized bituminous coal in a hot briquetting operation. In this fashion, the plastic properties of the raw coal are utilized to provide the binding strength of the briquette, with the heat being supplied by the sensible heat of the char, supplemented by external heat from combustion of a portion of the char, if necessary. As an option, pitch from the tar fractionation or pitch cracking step can be added as an additional binder, if required to improve the physical properties of the briquette. The briquettes, prior to carbonization, will contain 20% to 25% volatile matter, based on a feed of Illinois No. 6 coal.

The briquettes are then carbonized at 1850°F (1010°C) in either a vertical shaft furnace or another type of suitable furnace to produce form coke with 3% to 5% volatile matter. The caking characteristics of the coal fines should contribute to the production of briquettes with the required physical properties. The off-gas from the high-temperature carbonizer is combined with the gas stream exiting the mild gasification solids disengagement step, for additional recovery of fuel gas and condensables in the downstream processing steps.

Option III. Smokeless Domestic Fuel Production

In this option, shown in Figure I-85, the mild gasification char is combined with pulverized coal to make a briquette as in Option II. The briquettes are treated to produce a smokeless domestic fuel briquette suitable for use in home stoves or for district heating purposes.

Except for the briquetting/curing step, all of the process steps are similar to those described in Option I. The yields of gaseous and condensable products from the mild gasifier are identical to those shown for Option I.

Briquetting

The combined hot char and hot char fines from the mild gasification and solids disengagement steps are combined with pulverized coal, making use of the sensible heat contained in the char to achieve a controlled plasticity in the char/coal mixture. This provides the binding mechanism for briquette production. The briquettes are then cured by holding at a temperature of 650°F, resulting in the production of about 60 tons/day of fuel gas. This fuel gas is used to provide additional heat for in-plant uses, such as for the briquette curing operation.

Optionally, soft or hard pitch can be used as an auxiliary binder if it is deemed necessary to improve the physical properties of the briquettes.

The briquettes will contain approximately 20% volatile matter, based on a feed of Illinois No. 6 coal.

Revenue Potential for the Selected Process Schemes

Based on the market survey for the char and condensables, the three char utilization options for integrating the mild gasification process with existing coal preparation plants were analyzed for the potential economic incentives. Approximations were made of the capital costs and operating costs of the above three options by a simplified analogy to estimated costs for similar (but not identical) processes using factored adjustments for differences in plant scale.

The three process options analyzed here are based on the three process schemes illustrated in Figures I-83, I-84, and I-85 with a million tons/yr dry coal capacity. The gasification process incorporates coal liquids recovery and separation. The coal is assumed to be a high-volatile, high-sulfur Midwestern coal such as an Illinois No. 6 coal. The estimated current product prices at the plant gate are considered to be on the conservative side. Estimates of input feedstock costs were also made that include transportation costs to the plant gate. In this preliminary cost analysis, costs for sulfur-capture additives to the mild gasification process were not included. Also, the cost to generate steam or pressurized air was not included. It should be

noted that the net operating profit estimate does not include debt service charges or amortization.

Total plant investment and an estimate of total project capital requirements for each of the above process options are given in Table I-42. The approximate distribution of plant investment between the major process facilities is illustrated in Figure I-86. An estimate of the annual operating costs, including product credits are given in Table I-43. These costs are for the mild gasification, char and liquids processing only, and do not include those for the supporting coal preparation plant.

Table I-42. TOTAL CAPITAL REQUIREMENTS FOR SELECTED CHAR UTILIZATION OPTIONS

<u>Item</u>	<u>Option I</u>	<u>Option II</u>	<u>Option III</u>
Total Plant Investment	120	200	140
Initial Catalyst and Chemical Charges	--	--	--
Prepaid Royalties	1	1	1
Reproduction (Start-Up) Costs	10	10	10
Other Owner's Costs	9	9	9
Working Capital	9	9	9
Land	<u>1</u>	<u>1</u>	<u>1</u>
Total Capital Requirements (Mid-1987 Dollars)	150	230	170

Within the limitations of the simplified estimating procedures employed, the above estimates are expected to give a fair approximation of the relative magnitudes of the various components of capital and operating costs. They are considered adequate for examining trends and ranges in the probable process economics and price sensitivities. However, discretion in interpretation is recommended in view of their limited accuracy of the cost approximations.

From the estimated capital and operating cost estimates for the million tons per year conceptual mild gasification plant, the simple return on investment was compared for the three char utilization options, as shown in Table I-44.

Figure I-86. PROCESS OPTIONS -- DISTRIBUTION OF PLANT INVESTMENT

Table I-43. ANNUAL OPERATING COSTS AND PRODUCT CREDITS FOR SELECTED PROCESS OPTIONS
(Basis Annual Production Factor -- 90%)

Item	Value, \$/Ton	Option I		Option II		Option III	
		tons/std. day	\$10 ⁶ /yr	tons/std. day	\$10 ⁶ /yr	tons/std. day	\$10 ⁶ /yr
Purchased Commodities							
Coal (dry basis)	30	8000	78.8	3000	29.6	3000	29.6
Coal Fines	30	--	--	1290	12.7	1296	12.8
Electric Power	50 mil/kwh	3630 kw	1.4	10,670 kw	4.2	8900 kw	3.5
Lime	--	--	0.1	--	0.1	--	0.1
Waste Disposal	--	--	--	--	--	--	--
Catalyst and Chemicals	--	--	0.5	--	0.5	--	0.5
Maintenance Materials	--	--	1.4	--	1.9	--	1.7
Miscellaneous Supplies	--	--	0.2	--	0.2	--	0.2
Labor	--	--	1.2	--	1.2	--	1.2
Plant Management & Admin. Serv.	--	--	0.4	--	0.4	--	0.4
Technical Services	--	--	2.9	--	3.2	--	3.0
Plant Operations	--	--	2.7	--	3.0	--	2.9
Plant Maintenance	--	--	1.7	--	2.9	--	2.1
Property Taxes & Insurance	--	--	0.5	--	0.5	--	0.5
General Corporate Expenses	--	--	91.8	--	60.4	--	58.5
Total Operating Costs (mid-1987, \$)							
Product Credits							
Pitch (0.13/lb)	250	54	(4.4)	81	(6.7)	54	(4.4)
Pitch Coke (0.17/lb)	340	36	(4.0)	54	(6.0)	36	(4.0)
Light Oil (0.07/lb)	136	76	(3.4)	114	(5.1)	77	(3.4)
Medium Oil (0.06/lb)	120	220	(8.7)	266	(10.5)	220	(8.7)
Cresosote Oil (0.11/lb)	218	287	(20.6)	313	(22.4)	287	(20.6)
Phenols (0.08/lb)	156	1.2	(0.1)	1.2	(0.1)	1.2	(0.1)
Ammonium Sulfate (0.03/lb)	60	8.2	(0.2)	8.2	(0.2)	8.2	(0.2)
Char/Coal Blend	26	6812	(58.2)	--	--	--	--
Form Coke	80	--	--	2530	(66.5)	--	--
Domestic Fuel	70	--	--	--	--	2983	(68.6)
Total Credits			(99.6)		(117.5)		(110.0)
Net Operating Cost (Profit)			(7.8)		(57.1)		(51.5)

Table I-44. ECONOMIC SUMMARY OF THREE MILD GASIFICATION PROCESS OPTIONS

	<u>Total Capital Requirement</u>	<u>Annual Operating Costs</u>	<u>Annual Plant Revenue</u>	<u>Simple Return on Investment, %</u>
	-----	\$ millions	-----	
Option I				
Char to Utility Fuel	150	91.8	99.6	5
Option II				
Char to Form Coke	230	60.4	117.5	25
Option III				
Char to Smokeless Fuel	170	58.5	110.0	30

With the previously described estimates of char fuel value (adjusted for ash and volatile matter content), it appears that Option I, incorporating a mild gasification plant with char blending for utility fuel production would not be economically justifiable. This assessment could be revised should char combustion characteristics prove acceptable, and particularly if char post treatment for sulfur reduction were successfully demonstrated. However, the form coke and the smokeless fuel options, Options II and III, show potential for an acceptable return on investment. It should be noted that the by-product market values employed in Table I-43 to estimate the net operating profits are on the conservative side. However, the sensitivity of the product costs on the return on investment is difficult to determine, given the approximations involved in these preliminary economic analysis.

Bajura and Ghate¹⁰³ first explored in 1986 the economic considerations of various process options for a mild gasification process. The preliminary economic analysis in this report supports their conclusion that potentially attractive returns from a mild gasification process may be realized.

Process Commercialization Plan

Commercialization of the mild gasification process formulated by this technology development effort can proceed once it has been shown to be technologically and economically viable by detailed engineering design studies and economic analysis. A "first of a kind" commercial demonstration plant of 1000 tons/day, representing a single train gasifier in a three-train million tons/yr plant, can potentially attain an acceptable level of risk to the developers by the DOE providing financial and technical support. Under the

above circumstances, Peabody Holding Company, Inc. would consider taking the initiative to develop such a project.

Development of the project would require effort in several areas. First, a project team could be put together to include Peabody, IGT, Bechtel, DOE, and others. A necessary participant would be a utility willing to contract for the char/coal blend or a steel industry agreeing to buy the form-coke. Peabody Development Company, with its many utility clients and contacts, could be utilized to arrange and execute such an agreement. The demonstration project efforts would also involve developing a commercialization plan that deals with the technology's environmental, health, safety, and socioeconomic (EHSS) aspects. These will be evaluated based on the performance of the "first demonstration plant" for solid wastes, air emissions, water effluents, water demand, noise, labor requirements, health, and safety.

Installation of a mild gasification process would be done in phases starting with the option requiring the least capital expenditure, the char/coal utility fuel option, and proceeding to the form coke or domestic fuel option, depending on which market justified the additional investment. Installation of the first phase could be done at one of Peabody Coal Company's existing coal preparation facilities. This approach will facilitate the required integration of the preparation plant with the mild gasification process. A candidate location would be Peabody's southwestern Illinois facilities where several underground and surface mines produce over 5 million tons of Illinois No. 6 coal annually. The coal would be conveyed to a central preparation facility. The clean coal product from this preparation plant will be shipped to an adjacent 1800 MW plant and also loaded on barges for shipment to other utility customers. This location is approximately 30 miles southeast of the St. Louis metropolitan area where markets for the co-products already exist.

Demonstrated technical and economic viability, technical and financial support from DOE, a strong project team with an end user participant, and a good site location will all lead to rapid commercialization of the mild gasification process.

Timetable for Commercial Development

Table I-45 shows a commercialization timetable. The project, through cooperative agreement with DOE, becomes a commercial operation once demonstrated. This continued operation of the project adds an important dimension of long-term assessment of reliability, operating and maintenance cost confirmation, and overall operating efficiency. Such a continuing "demonstration" makes marketing that much more effective as time progresses.

Table I-45. COMMERCIALIZATION TIMETABLE

<u>Period</u>	<u>Event</u>	<u>Other Activities</u>
1988	<ul style="list-style-type: none">• Construct half-ton coal per day process development unit (PDU) facility and obtain technology development data	<ul style="list-style-type: none">• Analyze results to evaluate process performance• Publish results of investigation on mild gasification
1989-1990	<ul style="list-style-type: none">• Expand/modify PDU facility and conduct integrated mild gasification of coal to obtain continuous operation data for technology assessment• Design and construct a 24 tons/day process demonstration unit to obtain adiabatic process design and scale-up data	<ul style="list-style-type: none">• Finalize reactor design• Continue process performance evaluation to optimize material and energy utilization• Publish results of investigation on mild gasification• Plan marketing approach and strategy for selected process options• Investigate economics
1991-1992	<ul style="list-style-type: none">• Operate the process demonstration facility for process optimization• Team with steel and coal tar processing industries to solicit clean coal technology funds• Construct a minemouth commercial demonstration plant of 1000 tons/day capacity	<ul style="list-style-type: none">• Conduct technoeconomic analysis based on commercial demonstration plant results• Continue marketing efforts
1993-1994	<ul style="list-style-type: none">• Operate the commercial demonstration plant• Phased expansion of the demonstration plant to process 3000 tons/day coal or select a new plant site to build the first full-size commercial plant	<ul style="list-style-type: none">• Publish commercial demonstration plant results• Continue marketing efforts

Market Penetration Potential

Market penetration of a coal conversion technology such as mild gasification will be influenced primarily by proven (or anticipated) relative economics. Timing will be affected, however, by a number of other factors that include demonstration of the technology, status of development, government regulations, competition from petroleum, etc. For example, commercial gasification technology, as epitomized by the Texaco and Lurgi processes, have successfully operated at both prototype and commercial scale and yet have not had wide acceptance because of marginal economics and competition from alternative raw materials (petroleum and natural gas) and alternative processes (flue gas desulfurization, etc.).

Mild gasification shows promise of natural integration with existing coal preparation plants. Its primary char product has potential, on the basis of reduced cost, to enter an existing metallurgical coke market. This market area is currently experiencing a decline in availability of domestic coke and increasing reliance on imported coke. Alternatively, the char may be blended with the coal preparation plant fuel.

The condensable products may also enter an existing market for coal tar products. The tar processing industry is also experiencing a decline in availability of domestic tars (from coke production) and increasing reliance on imports.

Large-scale exports of form coke, chemical feedstocks, and smokeless fuel to potential markets in nearby Central, South American, and European countries could also support mild gasification -- an attractive domestic coal conversion industry.

Institutional Barriers

The institutional barriers for the mild gasification products are very well defined. The logical barriers include economic factors and compliance with environmental and hazardous chemical exposure regulations. The ability to convert indigenous high-sulfur coals to co-products that are environmentally acceptable, superior to existing alternatives, and at competitive costs, would assist in overcoming these barriers. The U.S. steel industry has long recognized that the availability of economically priced coke would restore their leadership in the international market. The proposed mild

gasification concept for the production of form coke is one way to achieve this goal.

The proposed demonstration project to use smokeless fuel in place of firewood in a Colorado community should show the economic and environmental benefits of the use of a coal product to replace wood. Projects of this type, along with publicity of the associated benefits, should assist in educating people to accept smokeless fuel in the U.S. and abroad.

The primary hurdle to overcome with respect to the condensable hydrocarbon market is the cost of imports. Minemouth plants, with enclosed vessels, handling, transport, and processing facilities should minimize emission control problems and hence reduce manufacturing costs. The first set of demonstration and commercial processes may find it beneficial to sell the entire condensate in bulk form to well-established tar processors, such as the Koppers Co. and the Reilly Tar and Chemicals Co.

In the next few years, as more information on the characteristics and economics of producing selected co-products become available, it will become easier to develop a commercialization and marketing strategy that is consistent with the need to overcome the institutional barriers.

Infrastructure for Transportation and Distribution

There are no special requirements of transportation and distribution. Technology is to be applied at the coal mines, which already has a highly developed infrastructure for the receipt and handling of coal and distribution of co-products. The proposed technology will fit into that infrastructure.

Availability of Manufacturing Infrastructure

The individual components of the process and its supporting peripherals present no novel construction requirements and can all be fabricated by existing technology; the manufacturing infrastructure is in place and can be expanded to meet the demand in the 1990's.

In general, the elements of the technology represent conventional process industry hardware (vessels, heat exchangers, pumps, conveyors, etc.), and the industrial production system can respond quickly to an increase in demand.

TECHNOLOGY DEVELOPMENT RECOMMENDATIONS

In the development of conceptual advanced mild gasification of coal, several technology development needs were identified for detailed investigation during Task 2, Bench-Scale Mild Gasification Study, and Task 3, Bench-Scale Char Upgrading Study. A summary of the technology development recommendations for the Tasks 2 and 3 studies is given below. Detailed test plans for the individual tasks were prepared after receiving DOE's authorization to proceed with these tasks.

Task 2. Bench-Scale Mild Gasification Study

Scope

- Coal characterization
- Effect of operating conditions on process performance in a two-stage, integrated entrained- and fluidized-bed reactor system:
 - Temperature = 1100° to 1500°F
 - Pressure = up to 50 psig
 - Particle size = -1/4 in.
 - Residence time = up to 20 minutes
 - Reaction gas medium = N₂, H₂O(g), CO₂, fuel gases and their mixtures
 - Feed and char withdrawal location = variable
- Effect of sulfur-capture additives (i.e., limestone and siderite) on co-product quality
- Effect of steam pretreatment of coal on process performance
- Effect of coal precleaning, using standard and advanced coal cleaning methods.

Purpose

- Performance of entrained- and fluidized-bed reaction stages in the selected reactor design
- Determine the effect of operating conditions and the type of reactor stages on product selectivity
- Conceptual design of commercial-scale integrated facility prepared in parallel, to establish requirements for process demonstration, for selected economic assessment of process alternatives.
- Selection of the optimal range of operating conditions
- Estimated process material and energy balances.

Discussion

The primary objectives of the Task 2 study are to obtain the process design data for the mild gasification of high-volatile bituminous coals, and to determine the effect of operating conditions on process performance in order to assess the control over product selectivity. The results from this study will be essential for conducting extended duration tests, and for determining the optimum operating conditions to selectively increase the yield of value-added co-products under Task 4. System Integration Studies.

Peabody Holding Co., Inc., has suggested a site for demonstrating the mild gasification technology. It is recommended that coals from this and other candidate sites are selected and characterized before conducting parametric tests to determine the effect of coal type, particle size (-1/4 in.), temperature (1100° to 1500°F or 593° to 815°C), pressure (0 to 50 psig), and devolatilization gas composition (steam, CO₂, fuel gas, or simulated flue gases), solids residence time (up to 20 minutes), and the performance of sulfur-capture additives and their role on devolatilization product yields.

Based on the literature review conducted thus far, and the reactor system selected for process development, it is appropriate to determine the process design data in a 100 lb/h reactor consisting of entrained- and fluidized-bed reaction stages. The results from this investigation will be useful to evaluate the performance of the selected reactor design.

As defined in the Statement of Work, the project team prepared a test plan for the bench-scale mild gasification studies and requested DOE-COTR authorization before starting the reactor design, construction, and testing with the selected coals.

Task 3. Bench-Scale Char Upgrading Study

Scope

- Char characterization
 - a. Elemental, minor, and trace element composition
 - b. Proximate analysis and heating value
 - c. Particle density, pore size distribution, surface area, and hardness
- Susceptibility to spontaneous oxidation
- Char ignition and combustion characteristics

- High-temperature mixing and briquetting of coal and char mixtures
- Evaluation of binders for briquetting char and char-coal mixtures
- Curing and carbonization of char and char-coal briquettes
- Reactivity of char (CO_2 gasification characteristics)
- Fluidized separation of char from char-limestone and char-siderite mixtures
- Regeneration of thermally decomposed and sulfided siderite
- Effect of limestone (used as a sulfur-capture additive) mixed with char on the combustion characteristics of the mixture
- Suitability of briquetted char and char-coal mixtures, with and without the sulfur-capture limestone, for smokeless fuel and metallurgical applications
- Steam-activation of char for high surface carbon use
- Steam posttreatment of char for reduction of sulfur content; examination of temperature requirements
- Conceptual design of commercial-scale integrated facility. Prepare in parallel with testing and incorporate economic assessment of selected process alternatives
- E-P toxicity tests with char leachates.

Purpose

To evaluate the suitability of char for the following applications:

- a. Char-coal mixture for utility fuel
- b. Smokeless fuel for domestic and industrial heating
- c. Form coke for metallurgical uses
- d. Adsorbent char

Discussion

The objectives of the Task 3 study are to generate the fundamental physical and chemical properties of the mild gasification char produced in the Task 2. Bench-Scale Mild Gasification Study, to evaluate the feasibility to produce the following forms of char product:

- Utility fuel
- Smokeless briquetted fuel for domestic and district heating purposes

- Form coke for metallurgical purposes
- Adsorbent char for industrial applications

The fuel applications would involve primarily the determination of solids handling and storage aspects, in particular the susceptibility to spontaneous oxidation. In addition, the rate of carbon burnoff will be determined in existing thermobalance reactors at IGT and compared with pulverized coal properties including its combustion characteristics.

The production of form-fuel would require bench-scale studies on briquetting, including the evaluation of alternative binders (that is, primary tar, coal tar pitch, and petroleum pitch), determination of the optimal binder requirements and briquette curing and carbonization conditions to produce either domestic fuel or metallurgical form coke. The primary emphasis of this investigation would be to produce a fuel that not only conforms with the specifications for utilization, but can also withstand handling for long distance or overseas transportation.

The chars produced from mild gasification experiments in Task 2 with limestone as sulfur-capture additive will be similarly characterized and tested for fuel and metallurgical applications. Whereas the residual char stream from studies with siderite, employed as a sulfur-capture additive, will be subjected to a systematic cold-model bench-scale fluidization investigation using existing equipment at IGT to determine the optimal conditions for separating the thermally decomposed and sulfided siderite from char. Following a Mossbauer characterization of the iron ore compound, the potential for regenerating it with steam-air mixtures, while preferentially producing elemental sulfur, will be investigated in existing thermobalance reactors at IGT.

The thermobalance reactors will also be useful for 1) conducting steam-activation of the char to produce adsorbent char, 2) examining the potential for steam post treatment for char sulfur reduction, and 3) determining the CO_2 -char gasification reactivity for synthesis gas production. The standard procedures for characterizing the char for these applications involving the measurement of surface area, pore size and pore volume distribution, E-P-toxicity of leachates, activation energy, and rate of reaction will be adapted.

The ash derived from the chars, with or without the sulfur-capture additive, will also be tested for the environmental impact of disposing the ash resulting from the combustion of char. The fate of the sulfur-capture additive will also be investigated.

The results from these bench-scale studies will form the basis for developing an integrated mild gasification process concept and reactor design consistent with the findings of the market assessment study.

20WP/61089tr3/RPP

REFERENCES CITED

1. Howard, J. B., "Fundamentals of Coal Pyrolysis and Hydropyrolysis," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 12, 665-783. New York: John Wiley and Sons, Inc. (1981).
2. Howard, H. C., "Pyrolytic Reactions of Coal," Chemistry of Coal Utilization, Suppl. Vol., Lowry, H. H., Ed., Chap. 9, 340-394, New York: John Wiley and Sons, Inc. (1963).
3. Talwalkar, A. T., "A Topical Report on Coal Pyrolysis," Dept. of Energy Report No. DOE/MC/19316-1408, February 1983.
4. Solomon, P. R., and Hamblen, D. G., "Measurements and Theory of Coal Pyrolysis, a Topical Report," U.S. DOE Report No. DOE/FE/05122-1668, July 1984.
5. Falbe, J., Ed., Chemical Feedstocks From Coal, 19-39. New York: John Wiley and Sons, Inc. (1977).
6. Che, S. C., et al., "Flash Pyrolysis Coal Liquefaction Process Development," Dept. of Energy Report No. FE-2244-26, 1978.
7. Protopapas, T. E., et al., "Annotated Review and Classification of Char Producing Processes," Vol. I, Dept. of Energy Contract No. DE-AC0-85FE6060, October 1987.
8. Seglin, L. and Bresler, S. A., "Low-Temperature Pyrolysis Technology," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 13, 785-845. New York: John Wiley and Sons, Inc. (1981).
9. Eisenhut, W., "High-Temperature Carbonization," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 14, 847-911. New York: John Wiley and Sons, Inc. (1981).
10. Wilson, P. J. and Clendenin, J. D., "Low-Temperature Carbonization," Chemistry of Coal Utilization, Suppl. Vol., Lowry, H. H., Ed., Chap. 10, 395-460, New York: John Wiley and Sons, Inc. (1963).
11. Aristoff, E., Rieve, R. W. and Shalit, H., "Low-Temperature Tar," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 16, 983-1002. New York: John Wiley and Sons, Inc. (1981).
12. Muder, R. E., "Light Oil and Other Products of Coal Carbonization," Chemistry of Coal Utilization, Suppl. Vol., Lowry, H. H., Ed., Chap. 15, 629-674, New York: John Wiley and Sons, Inc. (1963).
13. McNeil, D., "High-Temperature Coal Tar," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 17, 1003-1082. New York: John Wiley and Sons, Inc. (1981).
14. Scotti, L. J., et al., "Char Oil Energy Development Interim Report No. 5," Dept. of Energy Report No. FE-1212-5, August 1975.

15. Solomon, P. R. and Colket, M. B., "Coal Devolatilization," Proc. of 17th International Symposium on Combustion, Leeds, U.K., 131-143, 1979.
16. Solomon, P. R., "The Characterization of Coals During Thermal Decomposition," Proc. of the Fifth EPA Fundamental Combustion Research Workshop, Newport Beach, CA, 1980.
17. Arendt, F. and van Heek, K. H., "Comparative Investigations of Coal Pyrolysis Under Inert Gas and H₂ at Low and High Heating Rates and Pressures up to 10 MPa," Fuel 60, 779, 1981.
18. Tyler, R. J., "Flash Pyrolysis of Coals. Devolatilization of Bituminous Coals in a Small Fluidized Bed Reactor," Fuel 59, No. 4, 218-226, April 1980.
19. Solomon, P. R., "Experimental Study and Modeling of Coal Pyrolysis at High Temperatures," ACS Div. of Fuel Chem. Prepr. 24, No. 3, 154-159, 1979.
20. Che, S. C., Dolbear, G. E. and Longanbach, J. R., "Properties of Coal Liquids Produced by the Occidental Flash Pyrolysis Process," Proc. of the 1976 Coal Chemistry Workshop, Stanford Res. Inst., Menlo Park, CA, (1976) August.
21. Kobayashi, H., "Devolatilization of Pulverized Coal at High Temperature," Ph.D. Thesis, Massachusetts Institute of Technology, 1976.
22. Solomon, P. R. and Colket, M. B., "Evolution of Fuel Nitrogen in Coal Devolatilization," Fuel 57, No. 12, 749-755, December 1978.
23. Lester, T. W., Polavarapu, J. and Merklin, J. F., "Formation and Destruction of H₂S in the Short Residence Time Pyrolysis of Pulverized Coal and Model Compounds," Fuel 61, No. 6, 493-498, June 1982.
24. Suuberg, E. M. et al., "A Comparison of the Rapid Pyrolysis of a Lignite and a Bituminous Coal," ACS Div. of Petr. Chem. Preprints, 23, No. 1, 175-182, 1978.
25. Graves, R. L. and Fox, E. C., "Diesel Fuels From Minimally Processed Coal Liquids -- Exploratory Investigations," Proc. of Intersociety Energy Conversion Eng. Conf., San Francisco, CA, (1984) August.
26. Klein, J., "Untersuchungen zur Abspaltung von Wasserdampf, CO, CO₂, N₂, and H₂ bei der nichtisothermen Steinkohlenpyrolyse unter inerter und oxydierender Atmosphäre," Ph.D. Thesis, Aachen, FRG, 1971.
27. Freihaut, J. D., Seery, D. J. and Zabielski, M. F., "Investigation of the Devolatilization of Coal Under Combustion Conditions," U.S. DOE Report No. DOE/ET/10744-T4, January 1981.
28. McNeil, D., "Tar and Pitch," Kirk-Othmer Encyclopedia of Chemical Technology, 3rd Edition, Vol. 22, 566-600, New York: John Wiley and Sons, Inc. (1983).

29. Suuberg, E. M., "Rapid Pyrolysis and Hydropyrolysis of Coal," Sc.D. Thesis, Dept. of Chem. Eng., Massachusetts Institute of Technology, Cambridge, MA, 1977.
30. Sharma, D. K. et al., "Hydropyrolysis of Coal of Atmospheric Pressure Using Nascent Hydrogen," Erdoel und Kohle-Erdgas-Petrochemie **38**, No. 5, 236, May 1985.
31. Che, S. C. et al., "Effect of Carrier Gas on Tar Yield and Quality of Occidental Flash Pyrolysis," ACS Div. of Fuel Chem. Preprints, **24:3**, 111-121, 1979.
32. Fynes, G., Ladner, W. R. and Newman, J.O.H., "Coal Hydropyrolysis: Effect of Pressure on the Structure of the Tars and Chars," Proc. of Int'l Coal Science Conf., Dusseldorf, FRG, September 1981.
33. Sundaram, M. S., Steinberg, M. and Fallon, P., "Enhanced Ethylene Production via Flash Methanolysis of Coal," ACS Div. of Fuel Chem. Preprints **29**, No. 2, 129-140, April 1984.
34. Calkins, W. H. and Bonifaz, C., "Coal Flash Pyrolysis 5. Pyrolysis in an Atmosphere of Methane," Fuel, **63:12**, 1716-1719, December 1984.
35. Khan, M. R. and Jenkins, R. G., "Thermoplastic Properties of Coal at Elevated Pressures," Proc. of the 1985 Int'l Conf. on Coal Science, Sydney, Australia, October 1985.
36. McKinsey, R. et al., "Coal Pyrolysis for Utility Use," Report No. EPRI AP-5045, July 1987.
37. Hill, G. R. and Meuzelaar, H.L.C., "Differential Coal Liquefaction, an Economically Viable Way of Producing Liquid, Solid, and Gaseous Fuels," Proc. of New Fuel Forms Workshop (CONF-860271), 111-118, February 1986.
38. Khan, M. R., "Production of High Quality Liquid Fuels From Coal by Mild Pyrolysis of Coal-Lime Mixtures," Fuel Science and Technology Int'l, **5:2**, 185-231, 1987.
39. Graff, R. A. and Brandes, S. D., "Rapid Devolatilization of Steam-Treated Coal," Proc. of New Fuel Forms Workshop, CONF-860271, 36-47, (1986) February.
40. Regional Research Laboratory, Hyderabad, India; "Low Temperature Carbonization of Some Indian Coals," RRL Monograph Series **1**, 1986.
41. Rand, B., "Pitch Precursors for Advanced Carbon Materials-Rheological Aspects," Fuel, **66:11**, 1491-1503, November 1987.
42. Sharma, D. K. et al., "Comparative Studies of Pyrolysis of Coal in Inert Gas, Steam and Hydrogen," Erdoel und Kohle-Erdgas-Petrochemie, **39:4**, 173-176, April 1986.

43. Archer, D. H., Keairns, D. L. and Vidt, E. J., "Development of a Fluidized Bed Coal Gasification Process for Electric Power Generation," Energy Comm. 1, 115-134, 1975.
44. Goyal, A. and Rehmat, A. G., "Recent Developments in the U-GAS Process." Paper presented at the 17th Intersociety Energy Conversion Eng. Conf., Los Angeles, CA, August 1982.
45. Jones, J. F. et al., "Char Oil Energy Development, Final Report for the Period August 18, 1971 through June 30, 1975," Volume I, DOE Report No. FE-1212-T-9, Sept. 1975.
46. U.S. DOE Project DE-AC22-87PC79867, "Advanced Physical Fine Coal Cleaning-Agglomeration."
47. EPA 600/7-85-032, "Economic Evaluation of Oil Agglomeration for Recovery of Fine Coal," Aug. 1985.
48. EPA 600/7-86-017, "Evaluation of Conventional and Advanced Coal Cleaning Techniques," Sept. 1986.
49. Breuer, H. and Jungmann, A., "Sorting of Ultra-Fine Coal in Dilute Suspensions by Pneumatic Flotation," NR6/1985, Aufbereitungs Technik, 1985.
50. U.S. DOE Project DE-AC22-85PC81205, "Advanced Physical Fine Coal Cleaning -- Microbubble Flotation."
51. Attia, Y. A. et al., "Selective Flocculation Coal Cleaning for Coal Slurry Preparation," Proc. of 6th Int'l. Symp. on Coal Slurry Combustion and Technology, Orlando, FL, June 1984.
52. Attia, Y. A., "Cleaning and Desulfurization of Coal Suspensions by Selective Flocculation," Proc. of 1st Int'l. Conf. on Processing and Utilization of High-Sulfur Coals, Columbus, OH, Oct. 1985.
53. "Advanced Coal Cleaning Technology Assessment," NY State Energy Research and Development Authority, Report No. 87-5, May 1987.
54. "An Analysis of Chemical Coal Cleaning Processes," DOE/ET/10045-TI, June 1980.
55. McCown, F. E. and Im, C. J., "A Feasibility Study on Liquid Coal Preparation and Coal Char Demineralization," Final Report, DOE Report No. DOE/PC/60773-7, May 1985.
56. "Scaleup Slated for Coal Cleaning Method," Chem. and Eng. News, 32, Sept. 8, 1986.
57. "Pyrolysis of Coal for Production of Low Sulfur Fuel," EPRI AP-5005 Project 2051-2, Jan. 1987.
58. Khan, M. R. and Kurata, T. M., "The Feasibility of Mild Gasification of Coal: Research Needs." Technical Note DOE/METC-85/4019, July 1985.

59. Sass, A., "Clean Energy From Coal," paper presented at the A.I.Ch.E., 67th Annual Meeting, Washington, D.C., December 3, 1974.
60. Chu, C.I.C. and Gillespie, B. L., "Development of a Mild Gasification Process: Quarterly Report for the Period April-June 1987." Report to DOE/METC, DOE/MC/23289-2409.
61. Boley, C. C. and Fegley, M. M., "The Use of Char to Improve the Physical Quality of Coke." Paper presented at the Symposium on Technique and Use of Lignite, Grand Forks, N. Dakota, 165-174, USBM IC No. 8471 1970, May 1969.
62. Crynes, B. L., "Processing Coal Liquefaction Products," from Chemistry of Coal Utilization, Second Suppl Vol., Elliot, M. A., Ed., Chap. 29, 2020-2069, New York: John Wiley and Sons, Inc. (1981).
63. Merrill, L. G., Scotti, L. F. and Domina, D. J., "The Production of Clean Fuels From Eastern Coals by the COED Process." Paper presented at A.I.Ch.E. 79th Nat'l. Meeting, Houston, TX, March 1975.
64. Longwell, J. P. et al., "Coal Gasification and Tar Conversion Reactions Over Calcium Oxide." Proceedings of Fourth Annual Gasification Contractors' Meeting, Morgantown, W. V., Report No. DOE/METC-85-2, 291-302, Jan. 26, 1984.
65. Perch, M., "Coal Carbonization Processes (Carbonization)," in Kirk-Othmer Encyclopedia of Chemical Technology, 3rd Edition, Vol. 6, 298-302, New York: John Wiley and Sons, Inc. (1979).
66. McNeil, D., Coal Carbonization Products, Oxford, London: Pergamon Press Ltd., 1966.
67. The Condensed Chemical Dictionary, Ninth Edition, Van Nostrand Reinhold Co., 1977.
68. Edwards, J. H., Schluter, K. and Tyler, R. J., "Upgrading of Flash Pyrolysis Tars to Synthetic Crude Oil 1. First Stage Hydrotreatment Using a Disposable Catalyst," Fuel 64:5, 594-599, May 1985.
69. Feldkirchner, H. L. and Miller, R. L., "Upgrading Shale Oils Produced by the HYTORT Process." Paper presented at the Symposium on Synthetic Fuels From Oil Shale, Nashville, TN, October 1981.
70. Jones, J. F., "Pyrolysis of Oils Derived From Coal and Oil Shale in a Fluidized Bed of Catalysts." Paper presented at ACS Div. of Petr. Chem., 151st Nat'l. Mtg., Pittsburgh, March 1966.
71. Mrochek, J. E. and Scott, C. D., "Upgrading of Condensibles From Coal Devolatilization." From 7th Annual Gasification Systems Conference, Morgantown, W.V., CONF-870659-1, June 16, 1987.
72. Wachtel, S. J. et al., "Evaluation of Hydrotreated COED Syncrude -- Final Report," Memo No. MI.73-1, Atlantic Richfield Company, Jan. 1973.

73. Graves, R. L. and Fox, E. C., "Diesel Fuels From Minimally Processed Coal Pyrolysis Liquids -- Exploratory Investigations," Proc. of Intersociety Energy Conversion Engineering Conf., San Francisco, CA, Aug. 1984.
74. Knight, R. A., Babu, S. P. and Skelton, L. W., "Assessment of Chemical Feedstocks Production From Illinois Coal," Final Report for July 15, 1985-July 14, 1986, Grant No. 11CRG, Oct. 1986.
75. Wiedeman, J. P., "Roofing-Grade Coal Tar Pitches," Koppers Company, Inc. Bulletin, Sept. 1985.
76. Berber, J. S., Rice, R. L. and Fortney, D. R., "Thermal Cracking of Low-Temperature Lignite Pitch," ACS Div. of Fuel Chem. Prepr. 11, No. 2, 366-377, 1967.
77. Grosick, H. A., and Kovacic, J. E., "Coke-Oven Gas and Effluent Treatment," Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 18, 1085-1152, New York: John Wiley and Sons, Inc. (1981).
78. Khan, M. R., "Production of a High-Quality Liquid Fuel From Coal by Mild Pyrolysis of Coal-Lime Mixture," Technical Note, DOE/METC-86/4060, Morgantown Energy Technology Center, Morgantown, W.V., Mar. 1986.
79. Yeboah, Y. D., et al., "Effect of Calcined Dolomite on the Fluidized-Bed Pyrolysis of Coal," I&EC Process Design and Development, 19.4, 646-653, 1980.
80. Juntgen, H., et al., "Conversion of Coal and Gases Produced From Coal Into Fuels, Chemicals, and Other Products," from Chemistry of Coal Utilization, 2nd Suppl. Vol., Elliot, M. A., Ed., Chap. 30, 2071-2158, New York: John Wiley and Sons, Inc. (1981).
81. Energy Information Administration (EIA). "Coal Distribution," DOE/EIA-0125(87/29), January-June 1987.
82. Energy Information Administration (EIA). "Coal Distribution," July-December 1987.
83. Federal Energy Regulatory Commission, "Monthly Report of Cost and Quality of Fuel for Electric Plants," FERC Form 423.
84. Kolstad, C. D., Braden, J. B., Machado, J. A. and Woock, R. A., "A Market Survey and Assessment of the Potential for Desulfurized Illinois Coal," Institute of Environmental Studies, University of Illinois at Urbana-Champaign, 1987.
85. Wootten, J. M., "Clean Coal Technology, Economics for the Coal Producer." Presented at Comparative Economics of Clean Coal Technologies, Grand Junction, Colorado, 1987.
86. ICF Incorporated (ICF). Memorandum to Paul Schwengels, EPA, from Bruce Braine and Liz Nixon, ICF. Subject: Summary Findings of the "12 Million Tons of SO₂ Reduction Case," 1987.

87. Gushee, D. E., "Ozone and Carbon Monoxide Nonattainment, An Analysis of Title I of the Proposed Clean Air Standards Attainment Act," Congressional Research Service Report to Congress, 1987.
88. Temple, Barker & Sloane, Inc. (TBS). Economic Evaluation of S.321, "The Acid Deposition Control Act of 1987," The "Mitchell Bill," prepared for the Edison Electric Institute, 1987.
89. Electric Power Research Institute (EPRI), "Coal Markets and Utilities' Compliance Decisions," EPRI P-5444, 1987.
90. "1987 Census of North America Preparation Plants," Coal Age, 39-49, January 1987.
91. G. J. McManus, "World Steel," Iron Age, 15-19, Dec. 1987.
92. Technical discussions and consultations with Dr. M. Holowaty, Former Director of Research, Inland Steel Co., Gary, IN. Present Director, Environmental Research Laboratories, Indiana University, N.W., Gary, IN (Phone: 219-980-6666).
93. Technical discussions with Dr. S. Singh, Senior Engineer, Weirton Steel, Weirton, WV (Phone: 304-797-3788).
94. Technical discussions with Mr. Colin Henson, Rexco Ltd., Nottinghamshire, England (Phone: 011-44-623-860551).
95. Buttermore, W. H., "The Sulfur-tail Process: A Technique to Minimize Sulfur Emissions, Part I," Report No. 168, Coal Research Bureau, West Virginia University, Morgantown, WV, April 1979.
96. Telephone conversation with Mr. Marshall Owens, Sutcliffe, NV. Representative of Rexco (Phone: 702-673-9267) on Jan. 19, 1988.
97. "New Efforts to Promote U.S. Coal Hinted," Inside Energy, 1-2, November 16, 1987.
98. Technical discussions with Mr. F. M. Spinola, Plant Manager (until December 1987), Koppers Co., Inc., Chicago, IL. Now at Koppers Co., Inc., Corporate Headquarters, Pittsburgh, PA (Phone: 412-227-2744).
99. Technical discussions with Mr. Karl Leshner, Chairman, American Coke and Chemicals Association, Washington, D.C. (Phone: 202-452-1140), President, Reilly Tar and Chemicals, Indianapolis, IN (Phone: 317-248-6457).
100. Spaite, P. W., "Coal Tar Processing," Proc. of New Fuel Forms Workshop. Sponsored by Office of Coal Utilization, Advanced Conversion and Gasification, U.S. DOE, Washington, D.C., 100, May 1986.
101. Kiefer, D. M., "Profits Up Sharply as Producers Reap Benefits of Restructuring," C&EN, 26, December 14, 1987.
102. "Production Up Modestly in 1985," C&EN, June 9, 1986.

103. Bajura, R. A. and Ghate, M. R., "Mild Gasification: A 'Value Added' Process for the Coal Industry," Modern Power Systems, 31-33, October 1986.
104. Bristow, W. A., "The Development of Liquid Products From Low-Temperature Carbonization," J. of the Inst. of Fuel XX 113, 109, April 1947.
105. Howell, R. D., "Mechanical Design Considerations in Commercial Scale Coal Gasification Plants," Proc. of Sixth Synthetic Pipeline Gas Symposium sponsored by A.G.A., OCR and IGU, Chicago, IL, 317, Oct. 28-30, 1974.
106. Goyal, A. and Rehmat, A. G., "Recent Developments in the U-GAS Process." Paper presented at the 17th Intersociety Energy Conversion Engineering Conference, Los Angeles, CA, August 8-13, 1982.
107. Technical discussions with Mr. R. R. Severns, Senior Technologist (phone: 307 877-4475), FMC Corporation, Phosphorous Chemicals Division, Kemmerer, WY, during the months of December 1987 and January 1988.
108. Howard, J. B. et al., "Coal Devolatilization Information for Reactor Modeling," EPRI Report No. AP1803, Palo Alto, CA, 1981.
109. Landers, W. S. et al., Entrained Bed Carbonization of Bituminous Coal, R.I. No. 6608, Bureau of Mines, U.S. Dept. of Interior, Denver, CO, 1965.

APPENDIX A. Summary of Oil Shale Processing

SUMMARY OF OIL SHALE PROCESSING

Oil shale retorting has been practiced commercially since the mid-nineteenth century. However, such retorting has been primarily directed toward the production of oil, with only small quantities of gas production. These gases are usually consumed within the process to produce either heat for the retorting step or, in the more modern process concepts, hydrogen for upgrading the raw product oil.¹⁻²⁵ The quantity and quality of the gas produced depends upon the retorting process utilized. Some processes, especially those that utilize indirect heating or in-situ processing, can produce medium-Btu or high-Btu gas as a major co-product. A few processes are being developed for the primary production of manufactured gases. Also, in case of future need, the shale oil can be converted to gas in a secondary process step.

Resources

The world has very significant resources of oil shale. The energy content of the total recoverable world resources is estimated to be over 21,200 quads. The energy contained in this resource is more than the remaining recoverable combined world resources of natural gas, natural liquids, and crude oil.

The hydrogen content (per unit of carbon) of the organic matter in oil shales is higher than that in coals. Therefore, the conversion of carbon in oil shales to SNG requires less external hydrogen than that required for the conversion of carbon in coals.

Processing Technology

Several conversion processes have been tested for retorting and gasification at various scales of operation for the production of both liquid and gaseous substitute fuels. For the purpose of this report, the aboveground processes are considered.

The retorting processes are directed primarily at the production of oil, whereas the gasification processes are directed at the production of gaseous fuels ranging from low-Btu to high-Btu gas. Retorting processes can produce gas as a by-product, and some gasification processes can produce oil as a by-product.

Retorting Technology

Thermal retorting processes are defined as processes that involve heating of oil shale at near atmospheric pressure without the use of hydrogen or solvent in feed streams. Almost all processes developed at the large scale are thermal retorting processes.

The heat required for retorting is supplied either directly by combustion within the retort or indirectly by combustion outside the retort using the hot gases or hot solids produced to heat the feed shale. As mentioned earlier, the indirectly heated processes can yield some surplus fuel gas as a co-product.

The aboveground thermal retorting processes can be categorized as follows:

- Slow heat-up
 - direct gas heating
 - indirect gas heating
 - combination heating
 - hot-solids circulating
- Rapid heat-up
 - indirect gas heating
 - hot-solids circulating

Most of the aboveground thermal retorting processes are slow heat-up processes. Thermal retorting processes give oil yields that are within 10% of the yields estimated by the Fischer Assay, however the calorific value of gas produced varies with each process depending on the method of supplying heat to the retort.

In the direct heating processes, heat for retorting is generated within the retort by combustion of retorted shale and pyrolysis gas. These processes produce low-Btu gas because the gas formed in the retorting zone becomes diluted by carbon dioxide and nitrogen produced in the combustion zone. In the indirect-heating processes, heat is supplied by gas or solids (spent shale or heat transfer material) that are heated outside the retort vessel. In the combination heating processes, a gas sealing zone is usually incorporated inside the retort to eliminate mixing of gases between the directly and indirectly heated zones. The indirect and combination heating processes can produce medium-Btu and/or high-Btu gas.

Rapid heat-up processes are generally limited to laboratory-scale research in which small shale particles are injected into a hot fluidized bed retort. Rapid heating is believed to produce better yields than slow heating for similar types of shale. The type of gas produced is determined in the same manner as described above.

Another approach for processing oil shale, which at the moment is investigated mostly in academia, is sub- and supercritical extraction with various organic solvents or even with water. These processes yield some HCV gas as a by-product. However, in these processes more gas could be obtained by changing the temperature and/or residence time.

The term "hydroretorting" is generally used for retorting in the presence of hydrogen or hydrogen-rich gases. Hydroretorting has been conducted in both countercurrent moving-bed retorts and in cocurrent entrained-flow (flash hydrolysis) reactors. Because hydrogen-rich gas is used for retorting, these processes usually produce high-Btu gas as a by-product.

Because the composition of oil shales varies with the location of the deposit, different types of processing should be employed. The compositions of shales can be generally grouped into two major categories based on the hydrogen/carbon ratio of their kerogen. High yields (60% to 80% conversion of the organic carbon) can be achieved by thermal retorting of hydrogen-rich shales, such as those found in the Western U.S.A. However, for hydrogen lean shales, such as the clay-based Devonian shales found in the Eastern U.S.A., thermal retorting can convert only about 30% to 40% of organic carbon. Hydroretorting at elevated pressure, on the other hand, can improve yields by as much as 200% to 250%.⁴ In-situ processing should be used where the shale is too difficult or costly to recover by conventional mining techniques.

The Status of Thermal Retorting Technology

By 1984, many commercial-scale oil shale processing plants had been announced around the world.⁵ However, due to the significant softening of oil prices, and the closing of the U.S. Synthetic Fuel Corporation, most of the announced projects have been cancelled.

At present, commercial-scale oil shale retorting is being practiced in Brazil, China, Russia, and the United States. All commercially operated retorts use the aboveground thermal retorting processes.

In Brazil, Petroleo Brasileiro S.A. has been processing about 1790 TPD of oil shale by the PETROSIX process which incorporates a 18-ft-diameter retort.⁶ The plant, designed for 2460 TPD, was brought on stream in 1982. The PETROSIX retort is an indirectly-heated, moving-bed retort. In addition to the oil shale, the process also produces fuel gas. The shale processing facility is being expanded to include a new 36-ft-diameter retort.

In the Peoples Republic of China (PRC), two plants, located in Fushun (Northeast China) and Maoming (Southeast China), are processing oil shale. The PRC retort (225 TPD) was derived from early Japanese development efforts. The retort (about 10-ft diameter and 49-ft high) is a gravity flow, moving bed system employing hot gas from spent shale gasification in the lower section to pyrolyze the oil shale feedstock containing particles in the 8 to 20 mm size range as well as fines. There is no indication that China will do more than maintain its status quo in oil shale development.⁷

In Russia, the Kiviter and the Galoter retorts are used to process about 6 million tons per year of oil shale to produce oil and manufactured gas.⁷ The Kiviter retort, placed in operation in 1981, processes about 1110 TPD of oil shale. It is a moving-bed retort that processes coarse shale (25 to 125 mm) and has an annular chamber for preheating and drying of shale using recycle gas and a gas burner. The Galoter process handles a top size of 15 to 18 mm. It incorporates a rotating drum for retorting and uses spent shale heated by combustion of residual carbon in an ebulating bed. A 560 TPD plant has been operated successfully. The status of a 3700 TPD plant, expected to be constructed, is not known.

In the U.S.A., Union Oil of California is operating a facility designed to produce 10,400 bbl/day of shale oil using the Union B retort. This plant is currently operating at about 50% of design. In the Union B process, oil shale is fed at the bottom of the inverted-cone vessel. Hot gases enter the top and flow down countercurrent to the shale which is moved up through the retort using a solids pump. In addition to producing oil, the process also produces HCV gas. Plans to expand the production by 26,000 bbl/day are uncertain.⁵

Gasification Technology

Gasification of oil shales to produce manufactured gas as the primary product is not commercially practiced anywhere in the world. However, several processes are being developed to produce gas as the primary product.

IGT has conducted hydrogasification tests with several Eastern Devonian oil shales for the production of SNG. These tests have been conducted at various scales of operation, ranging from laboratory-scale batch tests in a thermobalance, through bench-scale tests to adiabatic PDU-scale tests (1 TPH). Moving-bed retorting tests have been conducted using cocurrent and counter-current contacting of gas and solids at pressures up to 35 atm and temperatures up to 1400°F. Operation at elevated pressures permitted high shale throughputs and achieved organic carbon conversions up to 87%.⁸

The flash fluid-slag gasification process has been developed by AB Svensk Alunskifferutveckling (ASA) of Sweden for black shale. This process gasifies a mixture of shale and limestone (about 10% by weight) with steam and oxygen at 2700° to 2910°F and atmospheric pressure to produce medium-Btu gas. The limestone promotes the formation of a non-leachable slag which is highly desirable in Sweden where previous oil shale industries have created environmental concerns about spent shale disposal. ASA has successfully completed operation of a 9 TPH pilot unit to test this process.⁹

In 1974, ASA conducted pilot-plant scale (6.7 TPD) fluidized-bed gasification tests using steam and oxygen, at temperatures in the range of 1650° to 1790°F, to produce medium-Btu gas.¹⁰ These tests achieved only 60% gasification efficiency, showed sintering problems at temperature above 1700°F and produced polycyclic hydrocarbons and pyrophoric coke. These pilot plants, located at Ranstad in Central Sweden, are now shut down and there are no plans for further development.

In 1985, IGT and HYCRUDE Corporation started research to determine the gasification characteristics of oil shales in fluidized beds using steam and oxygen to produce medium-Btu gas. Laboratory-scale test results are very encouraging, showing over 95% carbon conversion in 30 minutes at 1800°F and 2 atm pressure. In 1987, IGT used its U-GAS ash agglomerating coal gasification pilot plant to gasify 200 lbs of shale and produce spent shale in the form of non-leachable agglomerates.^{11,12}

In the PRC, a rapid pyrolysis of oil shale has been achieved by mixing it with hot charcoal in a moving-bed system. The ratio of charcoal to oil shale was 10:1. Products produced were largely gaseous including high-Btu gas, 4 wt % gaseous olefins and 1.4 wt % benzene.⁷

Table A-1 summarizes the status of current shale processes. Additional information can be found in References 14-25.

References Cited for Appendix A

1. International Gas Union (IGU) Report of Committee B -- Production of Manufactured Gases, pg. 53-56 (1985).
2. Janka, J. C. and Dennison, J. M. Devonian Oil Shale: A Major American Energy Resource. Paper presented at the IGT Symposium: Synthetic Fuels From Oil Shale, Atlanta, GA, December 3-6, 1979.
3. Punwani, D. V. Energy From Eastern Oil Shale: An Overview of Research Status. Paper presented at the 12th Energy Technology Conference, Washington, D.C., March 24-28, 1985.
4. Janka, J. C. and Rex, R. C., Jr. Application of the HYTORT Process to Oil Shales Throughout the World. Paper presented at the AIChE 1984 Summer National Meeting, Philadelphia, PA, August 19-22, 1984.
5. Barnes, H. H. Status of Commercial Oil Shale Development in the U.S. Paper presented at the 12th Energy Technology Conference, Washington, D.C., March 24-28, 1985.
6. Piper, E. M. The Petrosix Project in Brazil -- An Update. Paper presented at the Nineteenth Oil Shale Symposium, Golden, CO, April 21-22, 1986.
7. Uthus, D. B. International Developments in Oil Shale. Paper presented at the 12th Energy Technology Conference, Washington, D.C., March 24-28, 1985.
8. Feldkirchner, H. L., Weil, S. A., Janka, J. C. and Punwani, D. V. SNG From Eastern Oil Shale Via the HYTORT Process. Paper presented at the American Gas Association Transmission Conference, Salt Lake City, UT, May 5-7, 1980.
9. Hellestam, S., Strandell, E., Svemar, C. and Rex, R. C., Jr. Results of Flash Fluid Slag Gasification Tests on Swedish Alum Shale in the Slagging Gasification Reactor (SGE-3). Paper presented at the Nineteenth Oil Shale Symposium, Golden, CO, April 21-22, 1986.
10. Eklund, H. and Svensson, O. Reactor Model for the Gasification of Black Shale in the Fluidized Bed. Comparison With Pilot Plant Data. Ind. Eng. Chem. Process Des. Dev. Vol. 22 No. 3, (1983) pg. 396-401.

11. Lau, F. S., Rue, D. M., Punwani, D. V. and Rex, R. C., Jr. Gasification Characteristics of Eastern Oil Shale. Paper presented at the 1986 Eastern Oil Shale Symposium, Lexington, KY, November 19-21, 1986.
12. Punwani, D. V., Lau, F. S., Roberts, M. J., Hu, W.C.S. and Rex, R. C., Jr. Status of Current Research for Hydroretorting of Eastern Oil Shales. Paper presented at the Nineteenth Oil Shale Symposium, Golden, CO, April 21-22, 1986.
13. Young, D. C. An Investigation of the Feasibility of Recovering Energy From Antrim Oil Shale by an In-Situ Process. Final Report (No. FE-2346-94) prepared for the Department of Energy by the DOW Chemical Company, Midland, MI, September 1984.
14. Allred, V. D. Oil Shale Processing Technology. The Center for Professional Advancement, East Brunswick, New Jersey, 1982.
15. Rühl, W. Tar (Extra Heavy Oil) Sands and Oil Shales. Ferdinand Enke Publishers, Stuttgart, 1982.
16. Hunt, V. D. Synfuels Handbook. New York, Industrial Press Inc., (1983) pp. 293-403.
17. Meyers, R. A. Handbook of Synfuels Technology. McGraw-Hill Book Co., New York, 5-79, (1984) pp. 4-1.
18. Charlesworth, I. M. Oil Shale Pyrolysis: 1. Time and Temperature Dependence of Product Composition. Ind. Eng. Chem. Proc. Dev. Vol. 24, No. 4, (1985) pp. 1117-1125.
19. Charlesworth, I. M. Oil Shale Pyrolysis: 2. Kinetics and Mechanism of Hydrocarbon Evaluation. Ibid., pp. 1125-1132.
20. Sshmalfeld, I. Verfahrenstechnik bereit zur Verarbeitung von Ölschiefer und Teersand. Chem. Ind. Vol. 37, No. 6, (1985) pp. 407-411.
21. Carter, S. D. and Taulbee, D. N. Fluidized Bed Steam Retorting of Kentucky Oil Shale. Fuel Processing Technology. Vol. 11, No. 3, (1985) pp. 251-272.
22. Leftin, H. P. and Newsome, D. S. High Severity Pyrolysis of Shale and Petroleum Gas Oil Mixtures. Ind. Eng. Chem. Process Des. Dev. Vol. 25, No. 1, (1986) pp. 211-216.
23. Toreis, N., Verykios, X. E. and Grossmann, E. Catalytic Effects of Transition Metals on Oil Shale Pyrolysis. Ibid. No. 2, pp. 552-557.
24. Shi-Cai, G., Wei, H., Guang-Wei, H., Hao-Quqn, H., Rui, W., Hedden, K. and Wilhelm, A. Conversion of Chinese Oil Shales to Liquid Products Using Supercritical Extraction. Erdöl und Kohle-Erdgas-Petrochemie. Vol. 39, No. 7 (1986) pp. 311-316.
25. Hedden, K. and Missal, P. Extraction of Colorado Oil Shale Using Water as Solvent. Paper presented at the International Solvent Extraction Conference, München, FGR, Sept. 11-16, 1986.

Table A-1. STATUS OF VARIOUS SHALE PROCESSES

Process Name	Process Developer	Gas-Solid Contacting Mode	Heat Transfer Mode	Largest Scale Tested	Quality of Gas Produced	Status
Allis-Chalmers Roller Grate	Allis-Chalmers Corp., U.S.A.	Cross flow	Direct/indirect combination	680 kg batch	MCV	Dormant
Staged Turbulent bed	Chevron Oil Co. U.S.A.	Hybrid of co- & countercurrent	--	--	--	--
Dravo Circular Grate	Dravo Engineering Co., U.S.A.	Cross flow combination	Direct/indirect	300 t/d	LCV	Dormant
Fluidized bed	Kentucky Center for Energy Research, U.S.A.	Hybrid of co- & countercurrent	Indirect	45 kg/h	MCV	R&D continues to add spent shale gasification and combustion stages
Geokinetics	Geokinetics, Inc. U.S.A.	In-situ retorting	Direct	2000 bbl/d	LCV	Dormant
Lurgi-Ruhrgas	Ruhrgas A.G. and Lurgi, GmbH, FRG	Cocurrent	Hot solids recycle	12 t/d coal	MCV	--
Multi-solid	Battelle-Columbus Lab, U.S.A.	Hybrid of co- & countercurrent	Hot solids recycle	0.3 t/d	MCV	Dormant
OXY-VMLs	Occidental Petroleum Co., U.S.A.	In-situ retorting	Direct	37m (x) 37m (x) 62m	LCV	Dormant
PARAHO	The Paraho Development Corp. U.S.A.	Countercurrent moving-bed	Direct/indirect and combination versions	360 t/d	LCV/MCV	Dormant
Superior Circular Grate	Superior Oil Co. U.S.A.	Cross flow	Direct/indirect combination	250 t/d	LCV/MCV	Dormant
TOSCO	The Oil Shale Corp., U.S.A.	Cocurrent	Hot solids recycle	1000 t/d	MCV	Dormant
TJ	Government of Morocco	Fixed bed	Direct	3m-diam	LCV	Dormant
Union C	Union Oil Co.	Countercurrent	Direct	5000 bbl/d	LCV	Operating
HYTORT	IGT & HYCRUDE Corp., U.S.A.	Countercurrent moving bed	Indirect	24 t/d 35 bars hydrogen	MCV	R&D continues to expand data base
Hydrogasification and Pyrolysis	KWU GmbH Erlanger, FRG	Fluidized bed	Indirect	20 kg/d	MCV	laboratory scale
Flash Hydropyrolysis	Rockwell Int. U.S.A.	Cocurrent; entrained bed	Indirect 70 bars hydrogen	24 t/d	MCV	Dormant
Livermore Solids-Recycle Retort	Lawrence Livermore Laboratory, U.S.A.	Countercurrent moving bed	Hot solids recycle	2 t/d	LCV	Operating
CSIRO	Institute of Energy & Earth Resources, Australia	Fluidized bed	Hot spent shale recycle	27 kg/h	MCV	Operating
PRC	The Peoples Republic of China	Countercurrent moving bed	Direct, spent shale gasified	200 t/d	MCV	Operating
Kiviter	USSR moving bed	Countercurrent	Direct	1000 t/d	LCV	Operating
Galoter	USSR	Cocurrent	Hot spent shale	500 t/d	MCV	3000 t/d retort being designed

**APPENDIX B. Detailed Information on Sources and
References Used for Market Assessment**

DETAILED INFORMATION ON SOURCES AND REFERENCES USED FOR MARKET ASSESSMENT

Chemical Marketing Reporter is a weekly newspaper published since 1900 by Schnell Publishing Co., Inc., New York. It compiles and reports prices of most chemicals produced in the U.S. (f.o.b. plant). It also reports pertinent business and trade news concerning U.S. firms, features in-depth spotlight articles on selected commodities, and publishes an annual Chemical Buyers Directory.

Predicasts, Inc. of Cleveland, Ohio, produces computerized information retrieval services for a large variety of subjects. Two databases from Predicasts, Inc. were used to obtain marketing and product information for this report.

One database used was PTS PROMT which stands for Predicast's Overview of Markets and Technology. This is a multi-industry database that provides broad, international coverage of companies, products, markets, and technologies for all industries. It contains information from 1972 to the present and is updated weekly. Data in this file are comprised of textual and tabular abstracts from the world's trade and business journals, over 200 newspapers and regional business publications, newsletters, corporate news releases, corporate annual reports, industry studies by research organizations, and investment analyst reports by securities and investment research firms.

The other database used for specific product information was PTS U.S. FORECASTS. This database file contains abstracts of published forecasts for the U.S. and covers historical base data and forecasts of market information, imports, exports, prices, sales, profits, and other transactions of specific products. The sources of the information are from trade journals, business and financial publications, key newspapers, government reports, and specific studies from 1971 to present. Information in this file is updated quarterly.

SOURCE LIST

Data Sources

Chemical Marketing Reporter
Schnell Publishing Co., New York
(212) 732-9820

Predicasts, Inc.
Cleveland, Ohio
(216) 795-3000
(for database PTS PROMT and PTS US FORECASTS)

Annual Energy Outlook 1985
Energy Information Administration, DOE/EIA-0383(85)

Quarterly Coal Report, April-June 1987

Proceedings of New Fuel Forms Workshop, February 1986
Sponsored by U.S. Dept. of Energy, Office of Fossil Energy
Washington, DC

Encyclopedia of Chemical Technology, Ed. Kirk-Othmer

Trade Organizations

American Wood Preservers Institute
Vienna, VA
(703) 893-4005 Mr. John Hall

National Coal Association
Washington, DC
(202) 463-2625 Ms. Diane Moody

American Iron and Steel Institute
Washington, DC
(202) 452-7100 Mr. R. Jeffress

American Carbon Society
St. Marys, PA
(814) 781-8410 Mr. Leo Lanzel

Portland Cement Association
Skokie, IL
(312) 966-6200 Mr. Richard Smith

American Ceramic Society
Columbus, OH
(614) 890-4700 Mr. Greg Fischer

American Coke and Chemicals Association
Washington, DC
(202) 452-1140 Mr. J. Engle

Industry

Koppers Co., Inc.
Monroeville, PA
(412) 327-3000 Dr. K. Brzozowski; Mr. R. Thomas
Pittsburgh, PA
(412) 227-2000 Mr. R. Thomas; Mr. D. Sweet
Chicago, IL
(312) 242-1720 Mr. F. Spinola

Reilly Tar and Chemicals
Indianapolis, IN
(317) 248-6457 Mr. Carl Lesher, Mr. W. Roder

Merichem, Inc.
Houston, TX
(713) 455-1311 Mr. H. W. Pfenning

Weirton Steel Corp.
Weirton, WV
(304) 797-3788 Dr. S. Singh

Marblehead Lime Co.
Chicago, IL
(312) 263-4490 Mr. Richard Cusco

Hickman Williams Co. (coke + carbon products broker)
Oakbrook, IL
(312) 574-2150 Mr. John Seaman

USX Chemicals Division
Pittsburgh, PA
(412) 433-7562 Mr. J. Graeber

Allied Signal
Morristown, NJ
(201) 455-2000 Mr. S. Cohen

Western Tar Products
Terre Haute, IN
(812) 232-2384 Mr. M. Goeller

**APPENDIX C. Description of Other Potential Markets
for Coal-Derived Co-products**

DESCRIPTION OF OTHER POTENTIAL MARKETS FOR COAL-DERIVED CO-PRODUCTS

Pulverized Fuel

Pulverized fuel-fired furnaces may be broadly classified into two types according to whether these furnaces are designed for removal of ash in dry or in molten form. The dry ash furnaces are frequently referred as "dry bottom" furnaces, and the molten ash furnaces are normally called "slag tap" or "wet bottom" furnaces.

Dry ash furnaces are the more common of the two. The operation of dry ash furnaces, with regard to load range and fuel properties, is simpler, more flexible, and more reliable than that of slag tap units. Their main disadvantages are that they are usually bigger and that 80%-90% of the ash fired must be removed from boiler and precipitator hoppers in the form of very fine dust. The intent in developing slag tap units was to avoid the problem of dust disposal as much as possible, by getting the ash into a heavier, granular form and retaining much more of it in the furnace than is possible in a dry ash unit. In wet bottom units the streams of molten ash flowing from the furnace are chilled by cold water that breaks them into the desired coarse product. Ash retention of more than 80% has been achieved with some designs and the higher volumetric and area heat release rates reduce equipment cost.

However, a key feature of the dry bottom furnaces is that they are suitable for all ranks of coal from peat to meta-anthracite and for the lowest coal qualities as measured by high ash or moisture content, low heating value, low ash fusion temperature and high potential for slagging or fouling. As an example, a 350-MW unit operates on anthracite fines containing 15% surface moisture, 32% ash, and 6% volatile matter. This coal is fired alone with no supporting fuel from 25% to 100% load. At maximum output, the coal fineness is 85% to 90% through a 200-mesh sieve.

Another example is the full scale firing test conducted on a commercial anthracite-fired steam generator using 500 tons of COED char containing 4% to 6% volatile matter derived from a Utah A seam coal.¹ These tests conducted at several loads without ignitors or support ring fuel and for test runs lasting up to 18 hours, showed better combustion results than were experienced with anthracite in the same generator. The char combustibility appeared to be inferior to that of bituminous coals, yet it was proved that commercial steam

generators can definitely be designed for the COED char and most of the other residues resulting from gasification processes.

Fluidized Bed

Fluidized bed combustion was developed to take the place of pulverized coal and stoker fired systems to generate steam. Because of the nature of the combustion process, it is possible to control sulfur and nitrogen oxide emissions, to burn a wide variety of coals without encountering problems of slagging and corrosion, to reduce the amount of heating surface required, and to eliminate a large radiant furnace cavity.

Fluidized bed combustion (FBC) systems are of two types: atmospheric FBC (AFBC), and pressurized FBC (PFBC). The interest in PFBC is based on the recognition that as combustion pressure is increased, the size of the combustor is decreased, as is the heat transfer surface requirement, thus reducing investment cost.

Combustion in an FBC system takes place in a chamber called combustor. The fuel and sorbent are fed into the combustor, fluidized by air and burned at 1550° to 1650°F. The sorbent is fine-grained limestone which reacts with the sulfur dioxide released from burning the fuel to form calcium sulfate. The bed material in the combustor consists primarily of mineral matter from fuel, calcium sulfate and excess calcined lime.

Several commercial size FBC units have been operating since the early 1980's, using fuels ranging from anthracite culm to lignite, petroleum coke and bituminous coal with thermal efficiencies ranging from 88% to 98% depending upon the fuel type and air/fuel ratio. At one commercial plant (Scott Paper, PA), the steam production rate is 650,000 lb/hr with anthracite culm as the fuel, and with a 30% turndown capability.

Cement Kiln

The process of cement manufacture consists of the blending of raw materials to form a homogenous mixture, the "burning" of the mix in a long kiln to form a clinker material, and the grinding of the clinker with the addition of a small proportion of gypsum to a fine powder. Two processes are used, known as the wet and dry processes, according to whether the raw materials are ground and mixed in a wet or dry condition. In a variant of these processes, the semi-dry process, the raw materials are ground dry and then mixed with 10% to 14% water and formed into nodules before burning in the kiln.

Briefly, in the dry process the raw materials are crushed, dried in rotary driers, proportioned, and then ground in tube mills consisting of rotating steel cylinders containing a charge of steel balls or other grinding media. The mills are continuous in operation, being fed at one end and discharging the ground materials at the other. Two mixes, one high and one low in lime, are often prepared and blended in the required proportions in a silo with vigorous air circulation. The dry powder is fed to the kiln.

In the wet process, the method differs somewhat with the nature of the raw materials. When chalks and marls are used, the raw materials are broken up and incorporated in wash mills. The chalk and clay are fed in the required proportions to the wash mill together with sufficient water to form a liquid of creamy consistence. A number of radial arms attached to a vertical spindle carry iron rakes which break up the lumps of solid matter as the arms revolve. The solid material is reduced to a fine state of division and passes as a slurry through the screens in the walls of the wash mill. Any flints present in the chalk remain at the bottom of the wash mill and are removed periodically. When the raw materials are harder limestones and shales, the wash mill is inadequate to effect the reduction. The raw materials are in such cases crushed and fed to large tube mills and water added to the mill in the amount required to form the slurry. When hard limestone and clay are the raw materials the clay is usually fed to the tube mill already dispersed in the water. The finished slurry does not contain more than a few percent of material remaining on a 170 mesh, and its water content varies from 35% to 45% with different raw materials. The slurry is pumped to slurry tanks or basins in which both rotating arms and agitation by compressed air are used to keep the mixture homogeneous.

The rotary kiln in which the mixture is burned at 2400° to 2700°F is a long cylinder rotating on its axis and inclined so that the materials fed at the upper end travel slowly to the lower end. Here the fuel, pulverized coal, oil or natural gas, or combinations of these, is blown in by an air blast and ignited. The slurry is dried in the upper part of the kiln and the water driven off as steam, and then, as it descends the kiln, the dried slurry undergoes a series of reactions, forming in the most strongly heated zone granular masses, mostly from 1/8-in. to 3/4-in. diameter, known as clinker. At the lower end of the kiln, the clinker passes into coolers. The heated air

drawn from the coolers is used for the combustion of the coal, so providing an economical exchange of heat. The comparatively cool clinker then falls on to conveyers and is transferred to storage hoppers or passed directly to the grinding mills. The grinding is usually done in large three- or four-compartment tube mills which are usually water-cooled in order to help to dissipate the heat generated. A small quantity of gypsum is added during grinding to control the setting, and the finely ground cement passes to silos from which it is drawn for packing.

The heating of kilns in Great Britain is done mainly by burning pulverized coal, and this very efficient fuel was used for this purpose long before it was introduced into other industries. Waste blast furnace gas has also been used in Scotland. In the U.S. both oil and natural gas are in common use in addition to pulverized coal.

The clay or shale used in the raw materials for Portland cement manufacture may contain sulfur compounds, while the powdered coal used to fire the kiln also contains sulfur. Other fuels such as oil, natural gas and charcoal contain fewer sulfur compounds. Part of the sulfur is eliminated in the burning process but part appears in the cement clinker generally as alkali sulfates. The content varies usually from less than 0.1% SO_3 to 0.5%, but in the unusual cases where charcoal is the fuel, the SO_3 content may reach about 1% to 5%. It may also reach this value in clinkers from the cement-sulfuric acid process.

The ash of the coal used for firing a rotary kiln combines with the raw mix during burning and thus causes some alteration in the composition of the clinker. The ash consists mainly of silica, alumina and ferric oxide. The effect of the incorporation of the coal ash on the clinker composition is shown by the following data.²

	Cement I			wt %	Cement II		
	<u>Clinker Calculated</u>		<u>Clinker Found</u>		<u>Clinker Calculated</u>		<u>Clinker Found</u>
	<u>Raw Mix</u>	<u>From Mix</u>			<u>Raw Mix</u>	<u>From Mix</u>	

SiO ₂	14.33	22.18	22.96	13.50	22.02	22.33	
Al ₂ O ₃	4.32	6.68	6.78	3.43	5.60	5.53	
Fe ₂ O ₃	1.46	2.26	2.54	1.27	2.07	3.28	
CaO	42.69	66.08	63.95	40.76	66.49	64.40	
MgO and SO ₃	1.81	2.80	2.94	3.27	3.82	3.61	

It is seen that the coal ash causes a change in the composition of the clinker. In practice the composition of the raw mix is adjusted so as to allow for this change. It is commonly found that about two-thirds of the ash is taken up by the clinker and about one-third passes out of the kiln with the gases. The proportion of the ash which is absorbed into the cement mix depends partly on the type of kiln and the heat exchangers. Although some is absorbed in the mix in the high-temperature zone, some is carried out of the kiln by the gases.

Apart from its effect on the gross composition of the mix, the ash also causes a degree of heterogeneity in the clinker. The melting point of the ash is commonly within the range of 1900° to 2300°F and thus in the coal flame it is molten. Part of the ash is absorbed by the clinker nodules in the burning zone by precipitation on to their surfaces where it reacts with the already formed clinker minerals.

It has been shown that any waste fuel can be used as partial replacement of coal fuel. R. S. Huhta reported a worldwide survey which found that cement producers used sawdust, woodchips, cashew nuts, lignites, waste rubber from a shoe factory, coconut shells, landfill gas, battery cases, palm oil shells, charcoal fines, rubber tires and graphite dust as partial replacement fuels.³

The percentage of tires used as replacement fuel ranged between 5% and 20%. The cement producers have been using these tires for two to six years. When the tire percentage exceeded 20%, hydrogen sulfide was noticed in the flue gas. Only two producers said they had any experience with using graphite dust; one using it experimentally and another using it as up to a 10% replacement. The former producer has been using it experimentally for 5 years and the latter for 3 years. The graphite dust contained 28% ash. They reported no quality problems or dangerous emissions. Both producers said the greatest problem seemed to be obtaining a steady source of supply.

In Italy, Cementeria di Monselice converted their three rotary kilns from oil firing to pulverized coal firing in 1980. The coal was mixed with 0% to 75% petroleum coke. It was reported that the switching of fuel had no adverse effect on the specific fuel consumption and on the thermal efficiency of the rotary kilns.⁴

Lime Kiln

The mainspring of a lime plant is the kiln in which the limestone is calcined. These kilns are of various types (rotary, vertical, or fluidized). Of these kilns the vertical type, continuous or semicontinuous, is by far the most widely employed in the world. The United States is the world's leader in rotary kiln lime production with nearly 85% of the open market-lime capacity provided by this kiln.

Rotary kilns vary greatly in diameter and length from 5 X 60 ft to 13 X 450 ft. Average sizes have advanced; kilns less than 150 ft in length are rarely installed anymore. In the larger kilns the ratio of length to diameter generally extends between 30-40:1. The rotary is installed at an incline of 3° to 5° on four to six foundation piers and revolves on trunnions at each pier. Rotation speed is adjustable with variable speed drives and operates generally in the range of 30 to 50 s/rev. Kilns are lined with 6- to 9-in. of refractory brick. Stone is charged into the kiln at the elevated end and discharged at the lower end, moving countercurrent to the flow of combustion gases, derived from fuel injected at the lower end. Unlike vertical kilns, rotary kilns are only charged with a maximum of 10% stone, so that at least 90% of the interior space of the kiln is confined to the flame and hot gases.

The size of the kiln feed ranges between 1/4 to 2-1/2 inch. Sizes smaller than 1/4-inch contribute to the formation of a ring of packed material on the wall of the kiln, lack of uniformity in combustion, and a more serious dust-control problem. To minimize the fines most plants screen the kiln feed just before it enters the kiln or preheater. However, size distribution is also important; the more restricted the gradation, the more uniform the lime quality.

Solid, liquid, and gaseous fuels are employed, but pulverized bituminous coal is the most widely used and is blown into the kiln at the discharge end with primary air. Lump coal cannot be employed, so every coal-consuming rotary plant maintains its own pulverization equipment contiguous to the kilns. The majority of experience among lime plants indicates that superior thermal efficiencies are obtained with coal as opposed to gas, whether the gaseous fuel is derived from coal, oil, or natural gas. The exact reason for this anomaly has never been adequately explained, other than the nature of the heat transfer to the stone is more efficient, and coal has higher inherent heat value.

Pulverized coal offers one disadvantage in that it accentuates the problem of kiln ring formations more than gaseous fuels. A traditional, chronic problem with many rotary kilns is the formation of "rings" that gradually accumulate on the interior kiln linings. Unignited, pulverized coal tends to adhere to these rings along with accumulations of stone, and lime dust, and coal ash. Another cause of this build-up is uneven kiln temperature. If concentration of fuel gas is too high near the kiln lining, some of the small lime particles tend to fuse and adhere to the lining. Elimination of fines from the kiln feed, use of larger sized stone of a minimum of 1/2- to 1-in., the use of low ash coal, and finer and more uniform comminution of the coal tends to alleviate this problem. Most kilns that burn gas or oil report either minor or no trouble with rings. When rings become too thick, overall kiln performance is seriously impaired. So the kilns are cooled slowly and shut down. Then the rings are most commonly removed by shooting with specialized industrial guns. Rings also increase the attrition on refractory linings.

Great Britain employs bituminous coal, whereas Germany uses coke as a solid fuel. There are a number of inter-related properties for evaluating bituminous coal for lime burning but reactivity is the most important criterion, since this factor determines kiln temperature. It is coal of moderate to low reactivity that is most adaptable for lime burning. Thus hard metallurgical coke of low reactivity is suitable for lime burning.

Anthracite coal is an excellent fuel for lime burning since it is hard and has low reactivity, ash, and volatile matter, often its use is interchangeable with coke.

For all solid fuels the ash content should be as low as possible, and 8% is set as a maximum. Ash exerts a negative influence by absorbing heat; it fuses to kiln linings, accelerating deterioration, and when in direct contact with the lime ash vitiates the quality by introducing silica, alumina, etc.

Coke and anthracite produce higher average temperatures than all bituminous coals and may require closer controls to prevent overburning. Having little or no volatile matter, these fuels waste less thermal calories in gaseous state combustion. As a result, a lower ratio of coke or anthracite to stone is applied than with bituminous in mixed-feed kilns by about 15% to 20%. Low grade solid fuels such as lignites and peats are totally unsuitable

for lime burning because of their relatively poor heat values and high ash and volatile matter contents.

Comparative experiences of rotary kiln operators with different fuels has been reported based on a partial survey of the U.S. lime industry. Significant conclusions were:

1. A majority reported slightly higher capacities are achieved (5% to 10%) with natural gas than with pulverized coal.
2. There is a general decline in thermal efficiency ranging from 2% to 20% with natural gas as compared to pulverized coal.
3. Primary air along with natural gas is used as a combustion aid by 90% of plants.
4. A minority of plants use coal or oil as auxiliary fuels with natural gas.
5. For controlling combustion, 95% of kilns are equipped with instrumentation for analyzing stack gases for O_2 , CO_2 , and combustible gases.
6. The majority reported greater ease of combustion control with natural gas over coal and oil.
7. Opinions were divided on whether gas, coal, or oil provided longer refractory life. Pros and cons were in balance.

Coal-Fired Combustion Turbines

The outstanding success of combustion turbines in aircraft led to industrial applications and to the early realization that combustion turbines required "clean" fuels to achieve satisfactory performance records. Distillate fuels and natural gas were suitable, but residual fuel oil was marginal at best. But for widest applicability, combustion turbines have to be able to burn coals or coal-derived fuels to compete with pulverized-coal-fired steam generators on overall cost, performance, and reliability.

The earliest significant tests of a coal-burning gas turbine in the United States were conducted in 1953 and 1955 by the Locomotive Development Committee of Bituminous Coal Research. In the later tests, about 1400 hrs of operation was achieved over 83 days, at an average load of about 2900 hp; but the development was finally abandoned because of the accumulation of ash deposits in the combustor and localized wear on both stator and rotor blades.

At about the same time, in Canada, an experimental coal-burning, exhaust-heated gas turbine was operated, using a cyclone furnace to supply hot coal

combustion products to a tubular heat exchanger, which in turn heated pressurized air going to the gas turbine. Feasibility of the system was demonstrated. Coal ash was no more troublesome here than in any cyclone furnace and was not a major factor in stopping further work.

However, a coal-burning gas turbine of 1400 hp was operated experimentally in Australia in 1963. It used pulverized brown coal burned in a conventional tubular combustor, with 48 unit cyclones in parallel to remove particulates, mainly ash, from the hot gas stream going to the turbine. The solids were smaller than 40 microns, with the cleaned gases entering the turbine carrying about 3.5×10^{-4} lb of solids per pound of gas. Without the ash separator, wear on the second-stage turbine stator blades exceeded 2 mg/hr-cm², an excessively high rate; with the separator the wear rate was reduced by a factor of 70. Based on these tests, compared with operation using oil, it was concluded that the service life of the turbine burning coal probably would not exceed 3000 hours.

In a further effort to determine whether direct-fired, coal-burning combustion turbines might find a place in increasing the efficiency of coal-burning power plants, the Bureau of Mines in the mid-1960's tested the same turbine used by the Locomotive Development Committee a decade earlier. A new blade design was used to try to reduce erosion, but metal loss was still excessive, and it was estimated that the rotor blades would probably last 20,000 hr and the stator blades would have to be replaced after 5000 hr. Ash deposits also showed the presence of alkali metal sulfates, and much of the metal loss was attributed to corrosion rather than to erosion.

Thus, the problem of mineral matter in coal still provides the major stumbling block to the development of a successful combustion turbine to operate with direct coal firing. Recently, some progress has been reported in overcoming this problem. Highly cleaned coal-water mixture (CWM) combustion and deposition experiments have been performed by General Electric Co. (G.E.) using a modified gas turbine combustor and gas turbine nozzle sector.

G.E. performed combustion and deposition experimentation with their "Turbine Simulator." Its principal components are a modified J-79 aircraft combustor, an LM-500 aircraft derivative gas turbine first-stage turbine airfoil sector, and a connecting transition piece. The modified J-79 combustor was 16.5 cm in diameter and 45 cm in length. The plug-flow

residence time was approximately 20 ms. The nozzle cascade consisted of a 45° sector of the LM-500 first-stage turbine nozzle. The LM-500 is an aircraft derivative turbine with an output of approximately 5000 hp.

The CWM fuel used for the G.E. tests was supplied by Otisca Industries. Properties for the CWM are shown below. This fuel, which was prepared by micronization and physical separation of ash selective agglomeration, was selected based on its availability and likelihood that it would be most representative of a future gas turbine coal fuel.

Otisca Coal-Water Mixture Properties

Ash, %	0.8
Solids, %	50.0
Volatile matter, % dry	38-39
Sulfur, % dry	0.8
Particle size, micron (95% less than 15 microns)	4.0 mean

CWM fuel was fired at a rate of 400 lb/hr along with 40 lb/hr of fuel oil. The effect of the fuel oil was to reduce combustion delay because of slurry water vaporization and to enhance devolatilization. The combustor exit temperature was 2000°F and combustion efficiency, based on carbon in ash, was 99.5%. The residence time in combustor was 20 milliseconds. After 23 hours operation of the turbine simulator, ash deposition rates on a first-stage turbine nozzle sector were measured and were found to be much lower than would have been predicted from residual petroleum fuel experience because of differences in ash chemistry, and thus, deposition mechanism. The ash deposits were removed by different cleaning methods. Conventional cleaning by abrasive injection and water washing was found to be unexpectedly effective in the removal of coal ash deposits. However, improvements in cleaning methods or improving the deposit cleanability characteristics will be required to achieve acceptable cleaning levels.

The GE work is DOE-funded and it will be continued till the end of 1991. The overall objective of the work is to develop the technological basis necessary for the subsequent commercial development of a direct fired coal-fueled turbine power system. This system could be used in transportation and small stationary power applications. Components and systems required to achieve this objective in a cost effective and environmentally sound manner will be developed. The coal fueled gas turbine components developed will be

fabricated and incorporated into an LM-500 gas generator for integrated systems testing with the coal fuel.

Whereas GE is developing a coal-fueled combustor which sends ash with the combustion products to the gas turbine, there are other companies which are developing, also with DOE funds, direct coal-fueled combustors in which ash or slag is separated from the combustion products before sending them to the gas turbine. Solar Turbine, Inc. is developing a two-stage slagging combustor in which the ash is removed as slag. Allison Gas Turbine (a division of General Motors Corporation) is developing a "rich-quench-lean" combustor. Westinghouse is developing a slagging combustor in which a sulfur sorbent is added to remove sulfur as well. Foster Wheeler Development Corporation is developing a circulating pressurized fluidized bed combustor. All these combustors are scheduled to be ready by 1991.

While GE is developing a turbine combustor which requires a 4 micron coal particle and ash and sulfur each not exceeding 0.8 wt %, Solar Turbine, Allison, Westinghouse and Foster-Wheeler are developing combustors for which ash and sulfur contents are not critical because both of these constituents are removed in the combustors. Thus it appears that char, in spite of its high ash content, can be adapted as a fuel for gas turbines for all the turbine combustors except the GE combustor. For the GE combustor, char would have to be deashed and desulfurized.

Coal Firing of Blast Furnaces

Ironmaking energy costs for heating the charge of materials can be reduced by substituting coal for a portion of the coke charge, or as a replacement for currently injected fuels. Pulverized coal injection is routine practice at Armco's two Ashland blast furnaces and more than 1.7 million tons of coal had been injected by Dec. 1982. Annual savings were estimated at 10 million dollars over coke.⁵

In Japan pulverized coal injection facilities were first introduced at Nippon Steel Corporation's Oita No. 1 blast furnace, which has operated with the new technology since June 1981. Since then both the coal injection system and the blast furnace have operated without serious trouble. As a result of pulverized coal injection and lowering of fuel ratio, throughput has increased by 22%.^{6,7,8} Another 13% increase in throughput was achieved by controlling the tuyere nose conditions and by adjusting the burden distribution.⁹

Kobe Steel has also developed various techniques concerning pulverized coal injection systems and has applied them to large and medium scale blast furnaces. These systems have been operating since spring 1983 without any trouble and have contributed to the maintenance of a stable operation, reduction in energy cost, and increase in hot metal production in the blast furnaces. To further reduce the energy cost Kobe is considering increased use of pulverized coal and to use lower priced pulverized coal which contains high ash.¹⁰

Most commercial systems use pulverized coal (less than 0.075 mm) but British Steel Corporation (BSC) developed a system that uses granular coal (less than 3 mm) and thus avoids both the high capital cost of a coal pulverizer and the operating cost of fine grinding. The injection of granular coal has proved a successful practice at BSC's Scunthorpe Works blast furnace. Over 38,000 metric tons of granular coal has been injected in one blast furnace using a pilot plant and over 10,000 tons have been injected into blast furnace in less than three months. Furnace operation has been smooth since the introduction of coal injection at both furnaces. The second blast furnace has been operating above previous record output levels as the coal injection was introduced. The granular coal has yielded replacement ratios close to unity which are comparable to those attained by practices injecting pulverized coal. The operating data of the furnace indicate that granular coal gasification is completed in the furnace.¹¹

Bortz studied the combustion of pulverized coal under conditions simulating injection into a blast furnace. He tested four coals and characterized through visualization and measurements the effects of coal rate, blast temperature from 1650° to 2200°F, coal fineness, injection position and momentum, on the combustion of these coals. The performance of the coals was very dependent on the coal rank. The other parameters, particularly the coal flow rate, also had a strong influence on the combustion rate. The char combustion for all four test coals was slow, indicating that an assumption of complete combustion in the raceway region of a blast-furnace is probably invalid except at very reduced coal rates.¹²

Coal-Fired Magnetohydrodynamics

Magnetohydrodynamic power generation (MHD) is a method for the direct conversion of thermal energy to electric energy. In an MHD process, an

electrically conducting fluid flows through a magnetic field that is oriented perpendicular to the flow. In accordance with the same principles governing more conventional power generators, the interaction of the conductor with the magnetic field produces a voltage which can drive a current through electrodes and an external load.

There are two principal MHD cycles for coal fired applications, viz., open cycle and close cycle systems. In an open cycle MHD system, the fluid used in the generator is produced in a high-temperature, coal-fired combustor. This combustion gas must be at a sufficiently high temperature to produce free electrons by ionization, thereby making the gas an electrical conductor. The resulting gas temperature is typically in the range of 4600° to 4800°F. In order to achieve conductivity levels necessary for effective power generation, a small amount of an easily ionized alkali metal (e.g., potassium) is added in the combustion chamber as a salt (e.g., potassium carbonate). The high gas temperatures required for the MHD generator also provide the basis for the high plant efficiencies obtainable. Because the gases leaving the MHD generator are still at a relatively high temperature (typically 3700°F), the exhaust heat can be recovered and used to generate steam to produce additional electricity, or to provide process heat.

In a closed cycle system, thermal energy is transferred from a heat source (the coal combustor) through a heat exchanger to the working fluid which may be an inert gas or a liquid metal/vapor mixture. After furnishing energy to the MHD generator and other downstream components, the working fluid is fed back to the heat source. Closed cycle systems may find applications in small size electric generating plants.

Most R&D activities in coal-fired MHD electric power generation have focused on open cycle systems which, as a consequence, have progressed to more advanced levels of engineering development than that of closed cycle systems. Major accomplishments in the development and integration of topping cycle components have been achieved at the Component Development and Integration Facility (CDIF) in Butte, Montana, where DC electric power has been produced in an MHD generator at levels up to 2.0 megawatts, inverted to AC power, and fed to a commercial electric utility grid. Bottoming cycle process development has also been significant at the Coal Fired Flow Facility (CFFF) in Tullahoma, Tennessee, where NO_x and SO_x control in MHD systems has been

demonstrated at the 28 MW thermal level with a coal fired boiler. The recent installation of a baghouse permits the evaluation of particulate control as well.

Historically, the U.S. open cycle MHD program was focused on component development. In FY 1985, the historic program was redirected by the Department of Energy to a multiyear MHD program targeted on the achievement of proof-of-concept testing of an integrated 50 MW_(thermal) topping cycle and an integrated 28 MW_(thermal) bottoming cycle. Fiscal constraints and a reassessment of DOE priorities for fossil energy technologies resulted in a determination not to request funds for the MHD program in FY 1986.¹³

Recently, CDIF have published MHD power generation test results. A 50 MW_(thermal) coal-fired combustor was installed in conjunction with the MHD generator. These two components were operated for a series of tests over a range of conditions for several hours. These test results demonstrate significant progress of the coal-fired MHD technology development toward commercialization, in that they can be used to verify theoretical estimates of MHD performance at the 50 MW_(thermal) scale. These results verify the engineering feasibility of MHD power generation and provide data necessary for scale-up of the process.¹⁴

Westinghouse Electric Corporation in 1966 performed a feasibility study for the Office of Coal Research on coal burning MHD generation. The study included consideration of char as a fuel for the system. It was concluded from this study that a char-burning MHD plant has a number of advantages as compared with a coal-burning plant. These conclusions indicate strongly that char would be a preferred fuel for an MHD generating plant. It was noted that the higher ash content of the char might slightly increase the cost of slag removal from the combustor and ash handling.

The advantage of char is attributed largely to its lower hydrogen content, which results in fewer hydroxyl ions and fewer negative ions in the conductive gas as compared to the use of raw coal. Calculations of conductivity of the products of combustion from use of char showed a definite gain in conductivity as compared to the use of coal under the same combustion conditions and seed concentration.¹⁵

Special or Novel Applications in Development for Co-Products

There is ongoing research and development on various new or improved products from coal and coal liquids. The magnitude of the market impact of these products cannot be estimated accurately, but they all could have a significant impact.^{16,17}

One such area is in the production of high strength fibers from coal pitch. The uses for structural carbon now without any new innovation products are expected to have a \$1.2 billion market by 1993.¹⁸ Structural carbon or graphite products are used in aircraft, auto bodies, sports equipment, and as a fiber in textiles and special fabric products. Polyacrylonitrile (PAN) is used now to produce most of the carbon fibers. Use of mesomorphous pitch (pitch derived from low-temperature carbonization) to make fibers by a spinning technique needs further development to improve the fiber's tensile strength and resistance to elevated temperatures.¹⁹

In the area of new fuel forms or new processes, the work at Brookhaven National Labs²⁰ to produce a clean carbon particulate fuel along with a hydrogen-rich gaseous fuel may lead to a successful application of burning carbon from coal as an oil or water slurry in turbines and diesels. Essentially, the Brookhaven process utilizes hydrogasification to maximize methane production. The methane is then cracked to produce fine carbon black and a hydrogen-rich gas for recycle to the process or for fuel use. This process could possibly be coupled with a mild gasification process if the component yields and processing costs are favorable. The attractive feature here is that ash, sulfur, nitrogen and oxygen compounds are removed from the final product in the process.

Other work concerning developments in liquid fuels from coals involves upgrading techniques such as hydrotreating for diesel fuel and jet fuel applications. AMOCO is evaluating the process schemes to upgrade and evaluate the market potential for the oils and tars production from the Great Plains Lurgi Gasification Plant that uses lignite coals.^{21,22} The results of this DOE-supported work would be useful for reviewing the results of the market assessment study conducted during this project.

A novel process that was extensively studied by AVCO Everett Research Laboratory, Inc. involves electric arc heating of coal to produce acetylene.²³

An immediate quench of the hot gases freezes the acetylene species for subsequent separation. The acetylene is a useful chemical feedstock produced as an alternate to petroleum-based feedstocks.

References Cited for Appendix C

1. "The Combustion Performance of COED Char," FMC Corp. Interim Report No. 4, 1975.
2. Lea, F. M., The Chemistry of Cement and Concrete, 3rd Edition, 1971.
3. Huhta, R. S., "Wasteful Survey Report," Rock Products, p. 40, April 1985.
4. Radici, E. et al., World Cement, p. 6, February 1985.
5. Sexton, J. R. and Winnerstrom, J. M., "Blast Furnace Coal Injection: Long Proven, Now Commercial," Iron Steel Eng. (U.S.) 60, p. 33-41, January 1983.
6. Tamura, S. and Toad, S., "Blast Furnace Coal Injection Technology: Development and Outlook," Tekkokai (Japan) 33:10, p. 68-75, 1983.
7. Wakuri, S., "Operation of Pulverized Coal Injection Into Large Blast Furnace With High Top Pressure," Trans. Iron Steel Inst. (Japan) 24:8, p. 622-630, 1984.
8. Wakuri, S. et al., "High Feed Rate Pulverized Coal Injection at Nippon Steel Coroporation Oita No. 1 Blast Furnace," Tetsu to Hagane (Japan), 70:12, 1984.
9. Gohnoh, M. et al., "Pulverized Coal Injection and High Productivity Operation of Nagoya No. 1 Blast Furnace," Tetsu to Hagana (Japan) 7:14, p. 858, 1983.
10. Uenaka, T. et al., "Pulverized Coal Injection at a Blast Furnace," Proc. 44th Ironmaking Conference, Detroit, April 14, 1985.
11. Maldonado, R. et al., "Granular Coal Injection into a Blast Furnace at the Scunthorpe Works of the British Steel Corporation," Proc. 44th Ironmaking Conference, Detroit, April 14, 1985.
12. Bortz, S., "Measurement of Pulverized Coal Combustion Under Conditions Simulating a Blast Furnace Environment," Report to Commission of the European Committees, ESCS Contract 7210-AA/601, Luxembourg, 1983.
13. U.S. DOE Report to Congress on Emerging Clean Coal Technologies, DOE/S-0034, May 1985.
14. Lowry, W. E. and Staats, G. E., "CDIF Status Report: Coal-Fired MHD Power Generation Tests," Proc. 24th Symposium on Engineering Aspects of MHD, Butte, MT, June 24, 1986.

15. "Study of the Identification and Assessment of Potential Markets for Chars From Coal Processing Systems," Battelle Memorial Institute, OCR Research and Development Report No. 44, 1969.
16. Margolis, J. M., "Advanced Composites for Airframes and Car Bodies," CEP 83, No. 12, p. 44, December 1987.
17. Mark, H. F., "Textile Science and Engineering: Present and Future," CEP 83, No. 12, p. 44, December 1987.
18. Wright, M. A., "Structural Carbons: Cutting Edge -- Will We Be There?" Materially Speaking 4, No. 3, published by Materials Technology Center, Southern Illinois University, Summer 1987.
19. Edie, D. D., "Research into Pitch Based Carbon Fibers," Materially Speaking 4, No. 1, published by Materials Technology Center, Southern Illinois University, Winter 1987.
20. Steinberg, M., "Clean Carbon and Hydrogen Fuel From Coal and Other Carbonaceous Raw Materials," in Proc. of 1987 International Conf. on Coal Science, Maastricht, The Netherlands, Oct. 26-30, 1987.
21. "Penn State Tests Alternate Fuels," Coal & Synfuels Technology p. 8, Oct. 5, 1987.
22. "DOD Contracts Awarded by DOE," Coal & Synfuels Technology, p. 5, Dec. 7, 1987.
23. Patrick, A. J. and Gannon, R. E., "A 1 MW Prototype Arc Reactor for Processing Coal to Chemicals," in Radio Frequency/Radiation and Plasma Processing, Edited by Cheremisinoff, Farah, and Ouellette, Chap. 13, published by Technomic Publishing Co., Inc., 1985.

APPENDIX D. Typical Coal Quality

Illinois No. 6 Raw
Illinois No. 6 Washed
Pittsburgh No. 8 Raw
Pittsburgh No. 8 Washed

TYPICAL ANALYSIS
Analytical Services Department

Mine or Prospect:

Basis: RAW

Date: 10/01/86

Preparer:

Seam: 6

State: ILLINOIS

Approver:

PROXIMATE ANALYSIS (AS RECEIVED) (DRY)			ASH FUSION	
Moisture	12.5		Reducing Atmosphere	
Ash	22.5	25.7	Initial Deformation Temp, F	2000
Volatile Matter	30.4	34.7	Softening Temp, F(H=W)	2050
Fixed Carbon	34.6	39.6	Hemispherical Temp, F(H=1/2 W)	2100
BTU	8991	10275	Fluid Temp, F	2230
Sulfur	3.64	4.16	Oxidizing Atmosphere	
MAF BTU		13832	Initial Deformation Temp, F	2320
lb. SO ₂ / M BTU		8.1	Softening Temp, F(H=W)	2370
			Hemispherical Temp, F(H=1/2 W)	2410
			Fluid Temp, F	2500
ULTIMATE ANALYSIS (DRY BASIS)			ANALYSIS OF ASH (IGNITED BASIS)	
Carbon		58.4	Phosphorous Pentoxide (P ₂ O ₅)	0.2
Hydrogen		4.0	Silica (SiO ₂)	44.6
Nitrogen		0.9	Ferric Oxide (Fe ₂ O ₃)	21.4
Chlorine		0.05	Alumina (Al ₂ O ₃)	17.8
Sulfur		4.16	Titania (TiO ₂)	0.7
Ash		25.7	Lime (CaO)	6.9
Oxygen		6.79	Magnesia (MgO)	0.7
SULFUR FORMS (DRY BASIS)			Sulfur Trioxide (SO ₃)	5.0
Pyritic Sulfur		1.72	Potassium Oxide (K ₂ O)	1.70
Sulfate Sulfur		0.10	Sodium Oxide (Na ₂ O)	0.88
Organic Sulfur		2.34	Strontium Oxide (SrO)	0.03
WATER SOLUBLE ALKALIES (DRY BASIS)			Barium Oxide (BaO)	0.04
Sodium Oxide (Na ₂ O)		0.090	Manganese Dioxide (MnO ₂)	0.05
Potassium Oxide (K ₂ O)		0.010	ALKALIES AS Na₂O	
EQUILIBRIUM MOSITURE				0.51
	10.5		BASE/ACID RATIO	
FREE SWELLING INDEX				0.50
	2.0		SILICA VALUE	
HARDGROVE GRINDABILITY INDEX				60.60
	55		SLAG VISCOSITY T250	
				2310

All analyses are subject to revision due to additional coring, conditions specified in the coal supply agreement, actual operating conditions at time of mining, type of preparation at time of mining, or federal and state regulations. Analysis intended for informational purposes only.

Source : PROXIMATE ANALYSIS BASED ON ANALYSIS OF 93 CORES WITH 9"
of : EXTRANEEOUS ADDED. REMAINDER OF ANALYSIS BASED ON PRODUCTION
Information : AND CORE ANALYSES.

TYPICAL ANALYSIS
Analytical Services Department

Mine or Prospect:

Basis: WASHED

Date: 10/01/86

Preparer:

Seam: 6

State: ILLINOIS

Approver:

PROXIMATE ANALYSIS (AS RECEIVED) (DRY)			ASH FUSION	
Moisture	14.2		Reducing Atmosphere	
Ash	10.5	12.2	Initial Deformation Temp, F	2050
Volatile Matter	35.3	41.1	Softening Temp, F(H=W)	2110
Fixed Carbon	40.0	46.7	Hemispherical Temp, F(H=1/2 W)	2170
BTU	10675	12442	Fluid Temp, F	2290
Sulfur	2.95	3.43	Oxidizing Atmosphere	
MAF BTU		14177	Initial Deformation Temp, F	2335
lb. SO ₂ / M BTU		5.5	Softening Temp, F(H=W)	2385
			Hemispherical Temp, F(H=1/2 W)	2430
			Fluid Temp, F	2550
ULTIMATE ANALYSIS (DRY BASIS)			ANALYSIS OF ASH (IGNITED BASIS)	
Carbon		69.9	Phosphorous Pentoxide (P ₂ O ₅)	0.2
Hydrogen		4.9	Silica (SiO ₂)	50.2
Nitrogen		1.1	Ferric Oxide (Fe ₂ O ₃)	16.1
Chlorine		0.05	Alumina (Al ₂ O ₃)	18.8
Sulfur		3.43	Titania (TiO ₂)	1.0
Ash		12.2	Lime (CaO)	5.4
Oxygen		8.42	Magnesia (MgO)	1.1
SULFUR FORMS (DRY BASIS)			Sulfur Trioxide (SO ₃)	4.2
Pyritic Sulfur		1.15	Potassium Oxide (K ₂ O)	1.95
Sulfate Sulfur		0.06	Sodium Oxide (Na ₂ O)	0.93
Organic Sulfur		2.22	Strontium Oxide (SrO)	0.06
WATER SOLUBLE ALKALIES (DRY BASIS)			Barium Oxide (BaO)	0.02
Sodium Oxide (Na ₂ O)		0.075	Manganese Dioxide (MnO ₂)	0.04
Potassium Oxide (K ₂ O)		0.005	ALKALIES AS Na ₂ O	
EQUILIBRIUM MOISTURE				0.27
	10.5		BASE/ACID RATIO	
FREE SWELLING INDEX				0.36
	3.0		SILICA VALUE	
HARDGROVE GRINDABILITY INDEX				68.96
	55		SLAG VISCOSITY T250	
				2465

All analyses are subject to revision due to additional coring, conditions specified in the coal supply agreement, actual operating conditions at time of mining, type of preparation at time of mining, or federal and state regulations. Analysis intended for informational purposes only.

Source : PROXIMATE ANALYSIS BASED ON PRODUCTION.
of : REMAINDER OF ANALYSIS BASED ON PRODUCTION AND CORE ANALYSIS.
Information :

TYPICAL ANALYSIS
Analytical Services Department

Mine or Prospect: PREPARATION PLANT Seam: 6
Basis: WASHED State: ILLINOIS
Date: 10/01/86

PROXIMATE ANALYSIS (AS RECEIVED) (DRY)			ASH FUSION	
Moisture	12.8		Reducing Atmosphere	
Ash	10.2	11.7	Initial Deformation Temp, F	2050
Volatile Matter	36.0	41.3	Softening Temp, F(H=W)	2090
Fixed Carbon	41.0	47.0	Hemispherical Temp, F(H=1/2 W)	2150
BTU	10875	12471	Fluid Temp, F	2305
Sulfur	3.00	3.44	Oxidizing Atmosphere	
MAF BTU		14123	Initial Deformation Temp, F	2320
lb. SO ₂ / M BTU		5.5	Softening Temp, F(H=W)	2360
			Hemispherical Temp, F(H=1/2 W)	2410
			Fluid Temp, F	2510
ULTIMATE ANALYSIS (DRY BASIS)			ANALYSIS OF ASH (IGNITED BASIS)	
Carbon		69.1	Phosphorous Pentoxide (P ₂ O ₅)	0.2
Hydrogen		4.9	Silica (SiO ₂)	50.2
Nitrogen		1.2	Ferric Oxide (Fe ₂ O ₃)	16.1
Chlorine		0.10	Alumina (Al ₂ O ₃)	18.8
Sulfur		3.44	Titania (TiO ₂)	1.0
Ash		11.7	Lime (CaO)	5.4
Oxygen		9.56	Magnesia (MgO)	1.1
SULFUR FORMS (DRY BASIS)			Sulfur Trioxide (SO ₃)	4.2
Pyritic Sulfur		1.21	Potassium Oxide (K ₂ O)	1.96
Sulfate Sulfur		0.05	Sodium Oxide (Na ₂ O)	0.92
Organic Sulfur		2.18	Strontium Oxide (SrO)	0.02
WATER SOLUBLE ALKALIES (DRY BASIS)			Barium Oxide (BaO)	0.06
Sodium Oxide (Na ₂ O)		0.080	Manganese Dioxide (MnO ₂)	0.04
Potassium Oxide (K ₂ O)		0.005	ALKALIES AS Na₂O	
EQUILIBRIUM MOISTURE				0.26
		9.6	BASE/ACID RATIO	
FREE SWELLING INDEX				0.36
		2.5	SILICA VALUE	
HARDGROVE GRINDABILITY INDEX				68.96
		54	SLAG VISCOSITY T250	
				2465

All analyses are subject to revision due to additional coring, conditions specified in the coal supply agreement, actual operating conditions at time of mining, type of preparation at time of mining, or federal and state regulations. Analysis intended for informational purposes only.

Source : ANALYSIS BASED ON PRODUCTION.
of :
Information :

Product: 100% Raw Report date: 01-30-87

Division:

Plant/Mine:

Location: Monongalia County, WV

Seam(s) Mined: Pittsburgh

Shipped By: Monongahela Railway, providing access to Conrail,
Pittsburgh and Lake Erie and Baltimore and Ohio
Railways

Type Operation: Deep Mine
Longwall and Continuous Mining

Typical Proximate Analysis

	<u>As Received</u>	<u>Dry</u>	
Volatile Matter, %	37.13	39.10	
Fixed Carbon, %	48.11	50.67	
Ash, %	9.71	10.23	
Moisture, %	5.05	---	
Sulfur, %	2.96	3.12	
Calorific Value	12,929	13,617	<u>MAF</u>
Btu/lb.			15,169

Gieseler Fluidity

Max. Fluidity (ddpm)
Max. Fluidity Temp. °C

Starting Temp. °C
Final Temp. °C
Temp. Range °C

Arnu Dilatation

Max. Dilatation, %
Max. Contraction, %

Softening Temp. °C
Max. Contraction Temp. °C
Max. Dilatation Temp. °C

Grindability Index 59
Free Swelling Index 8
Oxidation, % Transmittance 100

<u>Ultimate Analysis</u>	<u>Weight % (dry)</u>
Carbon	74.60
Hydrogen	5.11
Sulfur	3.12
Oxygen	5.52
Nitrogen	1.42
Ash	10.23
Chlorine	0.12

<u>Form of Sulfur</u>	<u>Weight % (dry)</u>
Pyritic Sulfur	1.66
Sulfate Sulfur	0.00
Organic Sulfur	1.46
Total Sulfur	3.12

<u>Mineral Analysis of Ash</u>	<u>Weight % (Ignited Basis)</u>
Silicon Dioxide, SiO_2	40.82
Aluminum Oxide, Al_2O_3	23.41
Titanium Dioxide, TiO_2	1.00
Ferric Oxide, Fe_2O_3	21.40
Calcium Oxide, CaO	4.47
Magnesium Oxide, MgO	1.31
Potassium Oxide, K_2O	1.16
Sodium Oxide, Na_2O	1.19
Sulfur Trioxide, SO_3	4.04
Phosphorous Pentoxide, P_2O_5	0.82
Strontium Oxide, SrO	----
Barium Oxide, BaO	----
Manganese Oxide, Mn_3O_4	----
Undetermined	0.38

Fusion Temperature of Ash °F

<u>Oxidizing</u>	
Initial Deformation	----
Softening (H=W)	----
Hemispherical (H=1/2W)	----
Fluid	----
<u>Reducing</u>	
Initial Deformation	----
Softening (H=W)	----
Hemispherical (H=1/2W)	----
Fluid	----

Product: 100% Clean Report Date: 01-30-87

Division:

Plant/Mine:

Location: Monongalia County, WV

Seam(s) Mined: Pittsburgh No. 8

Shipped By: Monongahela Railway, providing access to Conrail,
Pittsburgh and Lake Erie and Baltimore and Ohio
Railways

Type Operation: Deep Mine
Longwall and Continuous Mining

Typical Proximate Analysis

	<u>As Received</u>	<u>Drv</u>	
Volatile Matter, %	37.33	39.50	
Fixed Carbon, %	51.15	54.12	
Ash, %	6.03	6.38	
Moisture, %	5.49	----	
Sulfur, %	2.64	2.79	
Calorific Value	13,469	14,251	<u>MAF</u>
Btu/lb.			15,222

Gieseler Fluidity

Max. Fluidity (ddpm)	32340
Max. Fluidity Temp. °C	416
Starting Temp. °C	356
Final Temp. °C	460
Temp. Range °C	104

Arnu Dilatation

Max. Dilatation, %	+274
Max. Contraction, %	- 30
Softening Temp. °C	337
Max. Contrc. Temp. °C	381
Max. Diltn. Temp. °C	477

Grindability Index 62

Free Swelling Index 8

Oxidation, % Transmittance 100

<u>Ultimate Analysis</u>	<u>Weight % (dry)</u>
Carbon	78.09
Hydrogen	5.28
Sulfur	2.79
Oxygen	6.06
Nitrogen	1.40
Ash	6.38
Chlorine	0.08

<u>Forms of Sulfur</u>	<u>Weight % (dry)</u>
Pyritic Sulfur	0.72
Sulfate Sulfur	0.00
Organic Sulfur	2.07
Total Sulfur	2.79

<u>Mineral Analysis of Ash</u>	<u>Weight % (Ignited Basis)</u>
Silicon Dioxide, SiO ₂	48.76
Aluminum Oxide, Al ₂ O ₃	22.52
Titanium Dioxide, TiO ₂	1.07
Ferric Oxide, Fe ₂ O ₃	14.80
Calcium Oxide, CaO	4.82
Magnesium Oxide, MgO	1.15
Potassium Oxide, K ₂ O	1.43
Sodium Oxide, Na ₂ O	1.05
Sulfur Trioxide, SO ₃	3.69
Phosphorous Pentoxide, P ₂ O ₅	0.71
Strontium Oxide, SrO	----
Barium Oxide, BaO	----
Manganese Oxide, Mn ₃ O ₄	0.00
Undetermined	

Fusion Temperature of Ash °F

<u>Oxidizing</u>	
Initial Deformation	2440
Softening (H=W)	2493
Hemispherical (H=1/2W)	2528
Fluid	2560
<u>Reducing</u>	
Initial Deformation	2103
Softening (H=W)	2169
Hemispherical (H=1/2W)	2210
Fluid	2377

APPENDIX E. Market Survey for Reduced-Sulfur Coal

MARKET SURVEY FOR REDUCED-SULFUR COAL

This survey will help assess the value of processes for removing sulfur from coal. The survey should be answered by the OFFICER IN CHARGE OF FUEL SPECIFICATIONS. It is very important that all questions be answered. All responses will be held in confidence. Please return the complete survey document within five days in the attached envelope. Questions can be addressed to:

**Dr. Charles Kolstad
CRSC Survey
University of Illinois
408 South Goodwin Avenue
Urbana, IL 61801**

(Questions?: Contact Rodger Woock at 217/333-9897)

- 1. a. Name of Company:**
b. Name and mailing address of officer in charge of fuel specifications:

c. If someone else is answering this survey, please give us your name:
- 2. Please answer questions in this survey with regard to the following generating station:**

This will be called the REFERENCE GENERATING STATION below.

1. INFORMATION ABOUT REFERENCE GENERATING SYSTEM

3. For each UNIT of the REFERENCE GENERATING STATION please indicate your boundary (maximum or minimum) procurement specification for the following coal characteristics.

	<u>Unit 1</u>	<u>Unit 2</u>	<u>Unit 3</u>	<u>Unit 4</u>	<u>Unit 5</u>
(a) Minimum BTU/lb (moisture free)	_____	_____	_____	_____	_____
(b) Maximum Sulfur Content (as received, measured lb/MMBtu)	_____	_____	_____	_____	_____
(c) Maximum Moisture Content (as received) (%)	_____	_____	_____	_____	_____
(d) Minimum Volatile Matter (by weight, moisture free)	_____	_____	_____	_____	_____
(e) Maximum Chlorine (by weight, moisture free)	_____	_____	_____	_____	_____
(f) Size Dispersion (Maximum % < 1/4")	_____	_____	_____	_____	_____
(g) Minimum Hargrove Grindability Index	_____	_____	_____	_____	_____
(h) Maximum Ash Content (by weight, moisture free)	_____	_____	_____	_____	_____
(i) Minimum T ₂₅₀ (ash fusion) Temperature (°F)	_____	_____	_____	_____	_____
(j) Maximum T ₂₅₀ (Ash fusion) Temperature (°F)	_____	_____	_____	_____	_____
(k) Minimum Ash Resistivity (ohms-cm)	_____	_____	_____	_____	_____
(l) Maximum Base/Acid Ratio of Ash	_____	_____	_____	_____	_____
(m) Maximum Fouling Index Computed Using Na ₂ O - K ₂ O	_____	_____	_____	_____	_____
(n) Maximum Na ₂ O as % of Ash Mineral Analysis	_____	_____	_____	_____	_____
(o) Maximum % Alkaline as Na ₂ O, Dry Basis	_____	_____	_____	_____	_____
(p) Maximum Slagging Index	_____	_____	_____	_____	_____

4. According to data from FERC Form 423, your major purchases of coal in late 1986 were, for plant :

DATE	SOURCE	QUANTITY(T)	SULFUR(X)	ASH(X)	PRICE(c)
10/86	CARTER MINING CO	415400	0.34	4.80	198.30
10/86	CARTER MINING CO	54700	0.34	4.80	198.50
11/86	CARTER MINING CO	367300	0.29	4.70	197.10
11/86	CARTER MINING CO	107100	0.29	4.70	197.10

5. The quantity weighted average price of the coal bought during that period was 197.71 c/MMBtu. For purposes of this survey, this price is referred to below as your REFERENCE PRICE. The quantity weighted average sulfur content of the coal was 0.31 %. The quantity weighted average ash content was 4.75 %.

6. To the best of your knowledge, what was the average volatile content (% weight, dry-basis) of the purchases during this period? (Calculate the quantity weighted average as the sum of the product of the volatility % times the quantity of each shipment divided by the total quantity received during the period.)
- _____

II. REDUCED-SULFUR SOLID FUELS

A reduced-sulfur solid fuel product is described below. Following the description, other characteristics and delivery conditions are listed. After carefully reading these descriptions, you will be asked to indicate how much of this product you would purchase for a particular price differential relative to the REFERENCE PRICE established above.

PRODUCT CHARACTERIZATION

<u>Proximate Analysis</u>	<u>% Weight</u>		<u>Ultimate Analysis</u>	<u>% Weight</u> <u>Dry Basis</u>
	<u>As Rec'd</u>	<u>Dry Basis</u>		
Moisture	6.57	N/A	Moisture	N/A
Ash	/	9.32	Carbon	76.81
Volatile	/	35.26	Hydrogen	4.92
Fixed Carbon	/	55.42	Nitrogen	1.75
		-----	Chlorine	0.10
		100%	Sulfur	0.95
			Ash	9.32
Btu/lb.	/	13,827	Oxygen (diff)	6.15
Sulfur	/	0.95		-----
Alk. as Na ₂ O	/	0.18		100%

<u>Ash Fusion</u>	<u>Reducing (°F)</u>	<u>Mineral Analysis</u> <u>of Ash</u>	<u>% Weight</u> <u>Ignited Basis</u>
Initial Deform.	2700+	Silica, SiO ₂	53.10
Softening (H-W)	2700+	Alumina, Al ₂ O ₃	29.95
Softening (H=1/2W)	2700+	Titania, TiO ₂	1.47
Fluid	2700+	Ferric Oxide, Fe ₂ O ₃	7.31
T ₂₅₀ Temp.	2900+	Lime, CaO	2.24
		Magnesia, MgO	1.13
		Potassium Oxide, K ₂ O	2.75
% Equilibrium Moisture	4.5	Sodium Oxide, Na ₂ O	0.79
Silica Value	83.25	Sulfur Trioxide, SO ₃	0.72
Base: Acid Ratio	0.17	Phos. Pentoxide, P ₂ O ₅	0.12
Free-Swelling Index	5	Strontium Oxide, SrO	0.19
Hardgrove Grind-	48@4.5%	Barium Oxide, BaO	0.12
ability Index	Moisture	Manganese Oxide, Mn ₃ O ₄	0.08
Fouling Index	0.09	Undetermined	0.03
Slagging Index	0.10		-----
			100%

ADDITIONAL CHARACTERISTICS AND DELIVERY CONDITIONS

It is VERY IMPORTANT that you envision the following conditions of this product and your purchase of it:

- [A.] It is available from a reputable and reliable supplier.**
- [B.] It will be delivered in rail cars or barges according to the usual specifications for the REFERENCE STATION.**
- [C.] It can be handled satisfactorily in available conveyors, blenders, pulverizers, etc. Its vulnerability to freezing, oxidation, and spontaneous combustion is well within industry norms.**
- [D.] The stated price will be subject to usual premia or penalties for variations away from the specifications listed above and you can specify rejection limits.**
- [E.] You are able to curtail purchases of other fuels without being penalized or jeopardizing your ability to purchase those fuels in the future.**
- [F.] Air pollution control regulations will remain at current levels.**

PLEASE BE IMAGINATIVE AND FLEXIBLE IN CONSIDERING WHETHER THIS FUEL COULD BE ATTRACTIVE AT THE RIGHT PRICE FOR PART OF YOUR FUEL PURCHASES.

III. BIDDING FOR THE REDUCED-SULFUR FUEL

Most fuel procurement is done by competitive bidding. Each bid provides a price and list of coal qualities and you are able to choose among the bids. The format here is different. You are given a price for the reduced sulfur product and asked how much you would purchase. You can choose any amount, from 0% of your total 1986 coal requirement to 100%. You should purchase some of this product if, by substituting it for some or all of your other coal, you can reduce the busbar cost of generating electricity.

7. Suppose that the reduced-sulfur fuel is offered in spot or long-term contracts at 86.5 % of the REFERENCE PRICE (developed in point 5 above).

This would make its price

$$\underline{86.5} \% \times \underline{197.71} \text{ ¢/MMbtu} = \underline{170.96} \text{ ¢/MMbtu}$$

At this price, approximately how much of this fuel (as a percentage of your 1986-coal usage) would you buy? (Use an "x" to mark one point on the following scale)

8. Was your answer 0% to the preceding question? (Circle one response) YES NO

If NO: Go to question 8

If YES: Relative to late 1986 coal prices, at what price would it be worthwhile to buy enough of this product to make up 5% of your fuel purchases (in tons)? (Use an "x" to mark one point on the following scale. Your reference price is indicated by ▼.)

9. For the product specified above, rate the following non-price characteristics as negative or positive influences on your overall evaluation of the quality of the product.

	<u>Very Negative</u>		<u>Very Positive</u>	
a) Volatility	1	2	3	4
b) Combustibility	1	2	3	4
c) Handling characteristics	1	2	3	4
d) Sulfur content	1	2	3	4
e) Ash content	1	2	3	4
f) Ash fusion	1	2	3	4
g) Ash resistivity	1	2	3	4
h) Alkaline content	1	2	3	4
i) Chlorine	1	2	3	4
j) Fouling	1	2	3	4
k) Slagging	1	2	3	4
l) Supply reliability	1	2	3	4
m) Contract terms	1	2	3	4
n) Compliance with current SIP	1	2	3	4
o) Possible changes in pollution standards	1	2	3	4

10. If you have additional comments about this survey, please write them below:

PLEASE RETURN THIS SURVEY IN THE ATTACHED, ADDRESSED AND STAMPED ENVELOPE WITHIN FIVE DAYS. RETURN TO:

Dr. Charles Kolstad
CRSC Survey
University of Illinois
408 South Goodwin Avenue
Urbana, IL 61801

(Questions? Contact Rodger Woock at 217/333-9897)

THANK YOU FOR YOUR COOPERATION.

**APPENDIX F. Adjustments to Fuel Cost and
Premium/Penalty Calculation Procedures**

Comparative Evaluation

Calculation of Adjusted Delivered Cost Per Million Btu

Supplier #1

Coal produced in Kentucky.

Price \$25.00/Ton F.O.B. Mine.

Transportation Cost: \$12.00/Ton

Guaranteed Analysis: 7% Moisture, 8% Ash (dry basis),
13,000 Btu/lb. (as received).

Price	=	\$25.00/Ton
Tax (5% of \$25.00)	=	1.25
Transportation	=	12.00
Ash Adj. [*] .1968 X 8 (Ash Factor X % Dry Ash)	=	1.574
Moisture Adj. [*] .02314 X 7 X $\left[\frac{38.25 \times 500}{13,000} \right]$	=	<u>.238</u>

(Moisture Factor X % Moisture X Delivered Cost
Per Million Btu).

Total Adjusted Delivered Cost = \$40.062/Ton

Adj. Delivered Cost per Million Btu	$\frac{40.062 \times 500}{13,000}$	=	\$ 1.5408
-------------------------------------	------------------------------------	---	-----------

*Ash and moisture factors vary from plant to plant and are subject to periodic update.

Supplier #2

Coal Produced in West Virginia.

Price \$24.75/Ton F.O.B. Mine.

Transportation Cost \$13.50/Ton.

Guaranteed Analysis 6% Moisture, 8.2% Ash (dry basis),
13,200 Btu/lb. (as received).

Price		=	\$24.75/Ton
Tax (5% of \$24.75)		=	1.237
Transportation		=	13.50
Ash Adjustment	[*] (.1968 X 8.2)	=	1.614
Moisture Adjustment	[*] .02314 X 6 X $\left[\frac{39.487 \times 500}{13,200} \right]$	=	<u>.208</u>
Total Adjusted Delivered Cost		=	\$41.309/Ton

Adjusted Delivered Cost per Million Btu = $\frac{41.309 \times 500}{13,200}$ = \$ 1.5647

Selection of Supplier #1 would result in the lower cost per million Btu.

*Ash and moisture factors vary from plant to plant and are subject to periodic update.

Coal Payment Adjustment
Premium/Penalty Calculations

- Assume coal was produced in Kentucky.
Price \$25.00/Ton F.O.B. Mine.
Transportation Cost: \$12.00/Ton.
Guaranteed Analysis: 7% Moisture, 8% Ash (dry basis),
13,000 Btu/lb. (as received).
- Tons Received: 50,000
Ash as received: 8.5%
Moisture received: 6.0%
Btu as received: 13,000

$$\text{Ash Adjustment: } 8 - \left[\frac{8.5}{1 - .06} \right] \times .1968 = \$(-.205/\text{Ton})$$

(Guaranteed % Ash - % Ash (Dry) Received) X Ash Factor.

$$\text{Moisture Adjustment: } (7-6) \times .02314 \times \left[\frac{38.25 \times 500}{13,000} \right] = .034$$

(Guaranteed % Moisture - % Moisture Received) X Moisture Factor X Delivered Cost Per Million Btu.

$$\text{Btu Adjustment: } 38.25 \times \left[\frac{13,100 - 13,000}{13,000} \right] = .294$$

(Delivered Cost per ton X Btu Received - Btu Guaranteed)

Total Adjustment \$.123/Ton

50,000 Tons X \$.123/Ton = \$6,150 Premium paid to Supplier.

*Ash and moisture factors vary from plant to plant and are subject to periodic update.

APPENDIX G. Form Coke Process Descriptions

FORM COKE PROCESS DESCRIPTIONS

The following is a description of the six most significant of the form coke processes developed and those that have actually produced enough coke for blast furnace trials.

1. The Ancit Process is a modification of a Dutch State Mines Process for the production of domestic smokeless fuel briquettes.^{1,2} This process utilizes a two-coal, hot briquetting technique for producing a form coke. A non-coking, low-volatile, anthracite coal is heated rapidly to about 1100°F in a horizontal retort. The hot gas from this step is then utilized to preheat the coking coal component to about 550°F. The two components are then mixed in a ratio of 75% non-coking coal and 25% coking coal, with a resulting mix temperature of 800° to 950°F. The mix is briquetted at this temperature and the briquettes are transported to an insulated holding bin where they harden while slowly cooling, thus improving their physical properties.

Work on the Ancit Process was initiated in 1950, and in 1952, a 5 tons/hr pilot plant was built near Limburg, Holland. The Eschweiler Coal Company acquired the process rights in 1967, and in 1971, a 275 tons/day demonstration plant was built in Alsdorf, West Germany. The Ancit formcoke is primarily being used as smokeless fuel; however, several tests lasting 3 to 4 days each were run on a small blast furnace at Thy-Marcinelle, Belgium. The results were discouraging because the product was not resistant to abrasion and its strength was relatively low.

2. The BFL Process is similar to the Ancit Process in its basic form.^{1,3} It is a two-component system using 65% non-coking coal, which is devolatilized at about 1400°F in a Lurgi Ruhrgas unit, and 35% coking coal, which is heat-dried. The two coals are mixed and then briquetted at an average temperature of 850°F. The green briquettes can be used directly or calcined at 1450° to 1650°F in a vertical shaft coker.

The BFL Process has been extensively developed on progressively larger units, starting with a bench-scale unit in 1960. The first pilot plant, with a capacity of 100 tons/day was erected in 1964, and by 1967, this pilot plant had produced formcoke in both the green and calcined briquette form which was used for two blast furnace trials at Rheinhausen in 1970. On the basis of these tests, a decision was made to build a 300 TPD demonstration plant in order to produce sufficiently large quantities of form coke briquettes for testing in different blast furnaces and under various conditions. The demonstration plant was built at Prosper, West Germany, in 1976, but after many operating and mechanical problems, was permanently shut down in 1978.

3. The HBN Process requires a blend of 85% low-volatile, non-coking coal and 15% coking coal.⁴ The coals are briquetted using a tar or pitch binder. Then the green briquettes are charged into a shaft coker where they are carbonized at about 1850°F in a closely controlled heating cycle. The briquettes are cooled in the lower zone of the coker where the recovered heat is recirculated to the high temperature zone in a recirculating gas stream.

HBN form coke produced at a 100-tons/day pilot plant at Douai, France, has been tested in blast furnaces during four separate experimental programs. The duration of each of the test programs was quite extensive, ranging from 29 to 58 days. However, during the tests, only about 25% of the by-product oven coke was replaced with form coke. The design of a 200,000 tons/yr HBN plant was completed in 1977, but no orders for construction of such a plant have been placed to date.

4. The Sapozhnikov Formcoke Process was developed at the Ukrainian Institute for Coal Research in the USSR in the late 1960's.^{1,5} In this process, a mixture of crushed medium- or high-volatile, weakly coking coals is heated in a series of fluidized beds with closely controlled temperature increases between beds. After the coal has been heated to about 950°F, it is briquetted hot without the addition of binder. The hot briquettes are then heated to about 1850°F in vertical ovens in order to complete carbonization.

Only two blast furnace tests using Sapozhnikov form coke have been carried out on a small blast furnace, and each test was limited to a duration of three days. The form coke replaced 100% of the by-product oven coke with good operating results. Soviet coke specialists in 1977 indicated that they had no plans to replace their 8-tons/hr pilot plant with a larger unit.

5. The DKS Process was developed as a joint venture by Didier engineering GmbH, Keihan Rentan Kogyo Co., Ltd., and Sumitomo Metals Industries, Ltd.⁶ This process requires the blending of 70% to 90% non-coking coal, up to 20% coking coal, and 10% pitch binder. This mixture is heated and briquetted in a vertical slot oven with either a bottom dump floor or an inclined bottom with a discharge door at the lower end. The coking process is not significantly different from the by-product oven process except that the product is in the form of briquettes of uniform size and shape. One necessary precaution is to ensure that the coal blend is maintained within a critical fluidity range; if the fluidity is too high, the coal will fuse together and the individual briquette form will be lost.

DKS formcoke was used experimentally in six different blast furnaces in Japan in trials of from 3 to 21 days. The results indicated that the DKS formcoke can be used without adverse effects as a replacement for up to 50% of the by-product oven coke on large blast furnaces. At the present time, the 10-oven DKS process experimental battery has been shut down, and no plans have been announced to build a commercial-size installation.

6. The FMC Process was one of the first processes to produce formcoke suitable for blast furnace use on a large scale.⁷ FMC's primary objective when developing the process was to produce coke suitable for their phosphorus furnaces. The early work led to the building of a demonstration plant at Kemmerer, Wyoming, in 1960 as a joint venture between FMC and U.S. Steel Corporation. The FMC coke process was designed to use a single non-coking coal as the raw material, in conjunction with a binder produced from the tar generated during the carbonization step. The coals best suited for this process are low-rank, high-volatile, subbituminous and bituminous coals that are mined in the

states west of the Mississippi. However, good coking coals, including medium-volatile, bituminous coals, have also been successfully processed. The Kemmerer plant has been running successfully and continuously since 1966.

The first step in the FMC coke process is the devolatilization of the finely ground coal to produce a calcinate containing about 3% volatile matter. This is accomplished in a series of three fluidized bed reactors, from which tar is also recovered and processed into binder. The calcinate produced is mixed with an appropriate amount of binder and briquetted. The green briquettes are cured at about 450°F in an oven and coked at about 1600°F in a combination shaft coker and cooler to form a hardened briquette.

Several blast furnace tests have been carried out with form coke from the FMC coke process. In 1962, FMC form coke was tested on the experimental blast furnace of U.S. Steel Corporation in Universal, Pennsylvania.^{8,9} Subsequent tests included tests at Armco Steel Corporation in 1967;¹⁰ one at the No. 3 blast furnace of British Steel Corporation in Cardiff, Wales, in 1972,^{8,9,11} and a 20,000 net ton test of FMC form coke briquettes at Inland's No. 5 blast furnace in 1973.¹²

References Cited for Appendix G

1. Dartnell, J., "Formed Coke -- Still Waiting in the Wings," Iron and Steel International, June 1978, p. 155.
2. Hermann, W. and Schmit, R., "The ANCIT Process," Agglomeration 77, SME-AIME, Vol. 2, 1977, pp. 970-995.
3. Peters, W., "New Techniques for the Production of Blast Furnace Coke From the Aspects of Enlarging the Coke Coal Base," Panel Discussion: Technological Challenge in Use of Non-Coking-Coals, International Iron and Steel Institute Meeting, Osaka, Japan, 1976.
4. Cordier, J. A. and Rochas, R., "hbnpc Formcoke Tests in USINOR Blast Furnaces," Agglomeration 77, SME-AIME, Vol. 2, 1977, pp. 996-1011.
5. Barker, J. E., "The Coking Industry in the USSR: Recent Developments and Current Trends," Journal of the Institute of Fuel, Vol. 40, September 1967, pp. 387-396.
6. Wagener, D. et al., "DKS Formed Coke Process Operation Results and Recent Developments," Ironmaking Proceedings, Vol. 36, 1977, pp. 507-515.
7. Work, J., "The FMC Coke Process," Journal of Metals, May 1966, pp. 635-642.
8. Joseph, R. T., "The FMC Coke Process -- Ten Years Later." Paper presented at 13th Biennial Conference of the Institute for Briquetting and Agglomeration, Colorado Springs, Colorado, August 1973.
9. Darrow, W. L., Saller, E. and Poast, J., "FMC Formcoke Furnace Testing," Iron and Steel Engineer, Vol. 50, No. 8, 1973, pp. 75-76.

10. Saller, E. and Joseph, R. T., "FMC Progress in Form Coke," Ironmaking Proceedings, Vol. 30, 1971, pp. 232-236.
11. Holgate, J. K. and Pinchbeck, P. H., "Use of Formed Coke: BSC Experience 1971/1972," Journal of the Iron and Steel Institute, Vol. 211, No. 8, pp. 547-566, 1973.
12. Strangway, P. K. and Holowaty, M. O., "Blast Furnace Test With 20,000 Net Tons of FMC Formcoke at Inland's No. 5 Blast Furnace," Ironmaking Proceedings, Vol. 37, pp. 352-368, 1978.

END

**DATE
FILMED**

6 / 19 / 92