NOTICE

**CERTAIN DATA
CONTAINED IN THIS
DOCUMENT MAY BE
DIFFICULT TO READ
IN MICROFICHE
PRODUCTS.**

MATERIALS COMPATIBILITY AND LUBRICANTS RESEARCH ON CFC-REFRIGERANT SUBSTITUTES

Chemical and Thermal Stability of Refrigerant- Lubricant Mixtures with Metal

Quarterly Report

1 February 1992 - 31 March 1992

Dietrich F. Huttenlocher

Spauschus Associates, Inc.
1575 Northside Drive, NW
Suite 410
Atlanta, Georgia 30318

March 31, 1992

**Prepared for
The Air-Conditioning and Refrigeration Technology Institute**

This research project is supported, in whole or in part, by U.S. Department of Energy grant number DE-FG02-91CE23810: Materials Compatibility and Lubricants Research (MCLR) on CFC-Refrigerant Substitutes. Federal funding supporting this project constitutes 93.94% of allowable costs. Funding from non-government sources supporting this project consists of direct cost sharing of 6.06% of allowable costs; and in-kind contributions from the air-conditioning and refrigeration industry.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

The U.S. Department of Energy and the air-conditioning industry support for the Materials Compatibility and Lubricants Research (MCLR) program does not constitute an endorsement by the U.S. Department of Energy, nor by the air-conditioning and refrigeration industry, of the views expressed herein.

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor the Air Conditioning and Refrigeration Technology Institute, nor any of their employees, nor of any of their contractors, subcontractors, or their employees, makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product or process disclosed or represents that its use would not infringe privately-owned rights.

COPYRIGHT NOTICE

(for journal publication submissions)

By acceptance of this article, the publisher and/or recipient acknowledges the U.S. Government's and the Air-Conditioning and Refrigeration Technology Institutes, Inc. (ARTI) rights to retain a nonexclusive, royalty-free license in and to any copyright covering this paper.

ABSTRACT

This report presents completed sealed tube stability test results for the R-123/mineral oil mixture and preliminary results for seven of the eighteen contracted refrigerant-lubricant mixtures.

The R-123 mixture was tested at 105°C, 150°C, and 175°C. The results obtained indicate that prolonged exposure to temperatures of about 150°C and higher will lead to rapid chemical deterioration of the R-123/mineral oil system. Chlorotrifluoroethane (R-133a) and trifluoroethane (R-143a) have been identified as decomposition products of R-123.

Testing at 150°C and 175°C have been completed for the HCFC refrigerants R-22, R-124, and R-142b with either mineral oil or alkylbenzene lubricants. These mixtures were very stable at the indicated temperatures. Testing at a higher temperature level will be necessary to define their upper temperature limits.

Similarly, partial test results are available for HFC refrigerants R-32, R-125, R-134a (two esters), and R-143a with pentaerythritol ester lubricants at the 150°C and 175°C temperature levels. Again, all five mixtures were found to be extremely stable at the test temperatures and additional testing will be needed to establish their upper temperature limits.

SCOPE

During the first quarter we started sealed tube stability tests on as many of the refrigerant-lubricant mixtures as we could procure. We were able to accomplish this for fourteen of the eighteen mixtures specified in the Contract.

By the end of the reporting period the following has been achieved:

1. Completed are sealed tube tests at three temperature levels, as well as all associated analytical work for one of the mixtures.
2. Sealed tube tests at two temperature levels and parts of the analytical work have been completed for eight more mixtures. Based on an almost complete lack of quantifiable chemical interactions at the two test temperatures, sealed tube aging at a third temperature (200°C) has been started on five of these eight mixtures.
3. Sealed tube tests at two temperature levels are in progress on five additional mixtures.
4. We expect to receive shortly the polyglycol fluids needed to start work on three additional mixtures.
5. Unknown at this time is the availability status of the E-134 refrigerant needed to complete the contracted work.

SIGNIFICANT RESULTS

Test results are presented in the form of individual data tables for each refrigerant-lubricant mixture. The tables are attached as an Appendix to this report. Following each data table are the gas chromatograms for the respective test samples. The numbering system used for the appendix tables and figures follows the order in which refrigerant/lubricant mixtures have been listed in all prior documents, i.e work statements and proposals, that is by increasing refrigerant designation numbers starting with R-22. This system will be followed in all future reports, quarterly and final.

Listed in the data tables are the following information:

- Contents of the sealed tubes reported in each table.
- Aging conditions.
- Visual observations on the contents of aged sealed tubes, including change of oil (liquid phase) color expressed in units of ASTM Standard D1500 color scale, the condition of the steel catalysts, formation of insoluble materials, etc.
- Chemical analysis results, such as gas chromatography of the vapor phase tube contents, chloride or fluoride content as appropriate, and oil analysis for mixtures containing either polyglycol or polyol ester fluids.

The data column following the chloride/fluoride ion analysis results is labelled "% Refrigerant Reacted". This value was calculated from the halide ion content measured and making the assumption that each halide ion generated is equivalent to the destruction of one refrigerant molecule. From past experience, this is a reasonable assumption at least for systems of low and intermediate reactivity. It is not valid for highly reactive systems where multiple chloride atoms are stripped from refrigerant molecules. As shown below, R-123 at 175°C falls into the latter category.

This first quarterly report contains data collected up to 31 March, 1992. Many of the tables will have empty spaces indicating only partial completion of aging and/or analysis tasks. Work at three temperature levels has been completed on only one mixture, R-123/mineral oil (Subsection 1, below). Work on all of the remaining mixtures is still incomplete.

The available results for HCFC refrigerants, other than R-123, are summarized in Subsection 2, and for the HFC refrigerants/pentaerythritol ester mixtures in 3, below. At this time analytical information is not yet available for HFC/polyglycol mixtures.

1. R-123/Mineral Oil.

The evaluation of this refrigerant-lubricant mixture was the only one completed at three temperature levels during the first quarterly reporting period. All results obtained are summarized in Table A-4 and Figures A-7 and A-8. From the data it is apparent that this mixture begins to react catastrophically at or slightly above 150°C. In Table 1, below, a summary is provided of the quantitative analytical information that has been developed for the R-123/mineral oil mixture - chloride ion content and gas chromatography results, both expressed in terms of "R-123 Reacted". Note the close agreement between these two determinations at the 150°C temperature level. We suspect the 4 minute eluent to be a R-123 derivative containing one less chloride atom, namely CH_2ClCF_3 or R-133a.

Table 1: STABILITY of R-123 with MINERAL OIL

Aging Temp.	%R-123 Reacted from Cl Analysis	%R-123 Reacted from GC Analysis (Eluent at -4 min)
105°C	0.045	Not detectable
150°C	1.560	1.7
175°C	81.0	42.1

At the 175°C level the amount of chloride ion found was much larger than that equivalent to the removal of one chloride atom per molecule. Most likely the initial monochloro decomposition product was destroyed at the higher aging temperature with generation of additional chloride ion. Removal of chlorine from R-133a produces

CH₃CF₃ or R-143a. A new GC peak appears on the 175°C chromatogram (Figure A-8) eluting at about 0.85 minute. Under identical GC operating conditions R-143a elutes at about 0.85 minute (see Figure A-31).

The R-123 tests lead to the following conclusions:

- A. In the presence of oil the refrigerant undergoes rapid chemical degradation at temperatures at or above 150°C.
- B. The primary chemical degradation path for R-123 seems to be dechlorination: R-123 > R-133a > R-143a.

2. Other HCFC Refrigerants with Hydrocarbon Lubricants.

Completed have been tests at 150°C and at 175°C with the following HCFC/lubricant mixtures:

- R-22/mineral oil (Table A-1 and Figure A-1)
- R-124/alkylbenzene (Table A-5 and Figure A-9)
- R-142b/alkylbenzene (Table A-15 and Figure A-29)

Compared to R-123 these mixtures are quite stable. Visual observations, GC analysis, and halide ion determinations, indicate very little, if any, reaction. Table 2, below,

Table 2: COMPARISON of HCFC/LUBRICANT STABILITY

Test Sample	Aging Temperature	% Refrig. Reacted (from Cl Analysis)
R-123/Mineral Oil	150°C	1.56
	175°C	40.6
R-22/Mineral Oil	150°C	0.001
	175°C	0.003
R-124/Alkylbenzene	150°C	0.008
	175°C	0.015
R-142b/Alkylbenzene	150°C	0.011
	175°C	0.014

affords a quick comparison of the HCFC mixtures based on the chloride analysis derived values of "% Refrigerant Reacted". Aging tests at 200°C have been started for the above three mixtures to obtain a better definition of their upper temperature usage limits.

3. HFC Refrigerants with Pentaerythritol Esters.

Completed have been tests at 150°C and at 175°C with the following HFC/pentaerythritol ester (PE) mixtures:

- R-32/PE (branched acid - Table A-2 and Figure A-3)
- R-125/PE (branched acid - Table A-6 and Fig. A-11)
- R-134a/PE (branched acid - Table A-13 and Fig. A-25)
- R-134a/PE (100 cSt - Table A-14 and Figure A-27)
- R-143a/PE (branched acid - Table A-16 and Fig. A-31)

All of the results obtained indicate that little, if any, refrigerant decomposition occurred. Table 3, below, illustrates this point and also compares the five test mixtures. All of these mixtures will next be tested at 200°C.

Table 3: COMPARISON of HFC/ESTER LUBRICANT STABILITY

Test Sample	Aging Temperature	% Refrig. Reacted (from F ⁻ Analysis)
R-32/PE, branched acid	150°C	0.002
	175°C	0.001
R-125/PE, branched acid	150°C	0.005
	175°C	0.005
R-134a/PE, branched acid	150°C	0.001
	175°C	0.001
R-134a/PE, 100 cSt	150°C	0.001
	175°C	0.001
R-143a/PE, branched acid	150°C	0.003
	175°C	0.002

COMPLIANCE WITH AGREEMENT

The work performed during the first quarter was in conformance with all requirements stipulated in the Work Statement for the contract, except for one minor deviation.

The Work Statement requires that all PAG and ester lubricants used for sealed tube preparation have "Acid Numbers" of less than 0.05. The 100 cSt pentaerythritol ester specified and supplied by Henkel/Emery (Emery 2928 - ISO 100) was found to have an acid number of 0.1.

Discussions with the supplier established that the value we measured is quite typical for this ester, and well within the manufacturing specification of 0.2 maximum. Also, while the supplier can prepare a small laboratory scale sample with an acid number of less than 0.05, this will not be achievable in full scale production. Based on this information we decided to use Emery 2928 ester as supplied to us, that is with an acid number of 0.1. This assures that the results we obtain with this type of ester will at least be representative of "real world" commercial products.

PRINCIPAL INVESTIGATOR EFFORT

The principal investigator participated during the first quarter in the following Contract activities:

- Procurement and purity analysis of refrigerant and lubricant samples
- Scheduling and supervision of sealed tube preparation
- Scheduling and supervision of analysis of aged tubes
- Evaluation of test results
- Preparation of required reports to ARTI, including monthly progress letters, abstract for presentation at Purdue Compressor Conference, and quarterly report.

Table A-1: STABILITY of R-22 with MINERAL OIL

Sealed Tube Contents:

Valve steel strip
1.0 cc (0.9 g) of Suniso 3GS
0.9 g of R-22

Aging Schedule:

14 days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance of Aged Tubes		Chemical Analysis		
	Color Change of Oil (ASTM)	Other Visual Observations	GC	Cl Ion (ug)	%R-22 Reacted
150°C	From 2.5 to 3.0	Steel: No change	No change	2.5	0.0007
175°C	From 2.5 to 3.0	Steel: No change	No change	10.0	0.0027
200°C	From 2.5 to				

FIGURE A-1

RUN # 12 FEB/26/92 14:56:53

AREA%	RT	AREA TYPE	NR/HIT	AREA%
0.34	2301	BB	0.052	0.135
1.28	1704800	PB	0.140	99.865

TOTAL AREA= 1707100
MUL FACTOR= 1.0000E+00

RUN # 13 JAN/16/92 14:57:

AREA%	RT	AREA TYPE	NR/HIT	AREA%
0.33	945	BB	0.053	0.0
1.25	2726800	PB	0.155	99.9

TOTAL AREA= 2727700
MUL FACTOR= 1.0000E+00

Table A-2: STABILITY of R-32 with PENTAERYTHRITOL
ESTER (Branched Acid)

Sealed Tube Contents:

Valve steel strip
1.0 cc (1.0 g) of Castrol SW32
1.0 g of R-32

Aging Schedule:

14 Days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance		Chemical Analysis			
	Oil Color Change (ASTM)	Other Visual Changes	GC	F Ion (ug)	R-32 Reacted	Oil Analysis
150°C	No change at 2.5	Steel: No change	No change	6.0	0.002	
175°C	No change at 2.5	Steel: No change	No change	4.7	0.001	
200°C	From 2.5 to					

FIGURE A-3

R-32 "As Received"

RUN # 2 FEB/19/92 00:56:24

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.34	1063	BB	0.053	0.045	
0.60	2367700	PB	0.080	99.955	

TOTAL AREA= 2368800
MUL FACTOR= 1.0000E+00

Tube CB-01 R-32/PE Ester (branched acid)

14 Days @ 150°C

RUN # 3 MAR/18/92 11:06:37

AREA%	RT	AREA	TYPE	AR/HT	AREA%
0.33	1506	BB	0.050	0.059	
0.58	2553000	PB	0.081	99.941	

TOTAL AREA= 2554500
MUL FACTOR= 1.0000E+00

Table A-4: STABILITY of R-123 with MINERAL OIL

Sealed Tube Contents:

Valve steel strip
1.0 cc (0.9 g) of Suniso 3GS
0.9 g of R-123

Aging Schedule:

14 days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance of Aged Tubes		Chemical Analysis		
	Color Change of Oil (ASTM)	Other Visual Observations	GC	Cl Ion (ug)	%R-123 Reacted
105°C	From 2.5 to 3.0	Steel: Brown stain	No change	98.7	0.045
150°C	From 2.5 to 7.0	Steel: Etched	Reaction Product: 1.7% ● 4 min	3,260	1.560
175°C	From 2.5 to >8.0	Black sludge, Steel: Etched, sludge deposits	Reaction Products: 2% ● 0.8 min 42% ● 4 min	169,440	81% if one Cl, 40.5% if two Cl

FIGURE A-7

R-123 "As Received"
(Base Line)

RUN # 14

JAN/16/92 15:25:30

AREA%

RT	AREA	TYPE	AK/HT	AREA%
0.34	1060	BB	0.054	0.105
9.98	3051000	BB	1.711	99.895

TOTAL AREA= 3055000
MUL FACTOR= 1.0000E+00

Tube CD-01
R-123/Mineral Oil
14days @ 105°C

RUN # 7

FEB/19/92 10:24:04

AREA%

RT	AREA	TYPE	AK/HT	AREA%
0.34	1419	BB	0.052	0.100
11.10	1307100	BB	1.423	99.892

TOTAL AREA= 1308600
MUL FACTOR= 1.0000E+00

FIGURE A-8

RUN # 5 FEB/26/92 10:02:42

RET	AREA	TYPE	NR/HI	AREA%
0.34	9678	FB	0.050	0.663
1.17	795	FB	0.102	0.054
4.07	25207	BB	0.400	1.726
10.87	1424700	BB	1.473	97.557

TOTAL AREA= 1460400
MIN. FACTOR= 1.0000E+00

RUN # 7 FEB/26/92 10:42:11

RET	AREA	TYPE	NR/HI	AREA%
0.34	6012	BY	0.052	0.520
0.84	1427	VB	0.053	0.111
1.01	25017	FB	0.107	2.001
3.94	2790	BB	0.202	0.216
11.26	543500	FB	0.410	42.127
12.65	709010	BB	1.355	55.010

TOTAL AREA= 1290100
MIN. FACTOR= 1.0000E+00

Table A-5: STABILITY of R-124 with ALKYL BENZENE OIL

Sealed Tube Contents:

Valve steel strip
1.0 cc (0.9 g) of Zerol 150
0.9 g of R-124

Aging Schedule:

14 days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance of Aged Tubes		Chemical Analysis		
	Color Change of Oil (ASTM)	Other Visual Observations	GC	Cl Ion (ug)	%R-124 Reacted
150°C	No change at 2.0	Steel: No change	No change	18.4	0.008
175°C	From 2.0 to 2.5	Steel: No change	No change	38.1	0.015
200°C	From 2.0 to				

FIGURE A-9

RUN # 26 JAN/17/92 15:59:17

AREA%	RT	AREA TYPE	AR/HIT	AREA%
0.34	965	BB	0.054	0.025
2.56	3850100	PB	0.380	99.975

TOTAL AREA= 3851100
MUL FACTOR= 1.0000E+00

RUN # 9 FEB/26/92 11:34:49

AREA%	RT	AREA TYPE	AR/HIT	AREA%
0.34	1217	BB	0.053	0.086
2.72	1423000	PB	0.322	99.915

TOTAL AREA= 1424200
MUL FACTOR= 1.0000E+00

Table A-8: STABILITY of R-125 with PENTAERYTHRITOL
ESTER (Branched Acid)

Sealed Tube Contents:

Valve steel strip
1.0 cc (1.0 g) of Castrol SW32
1.0 g of R-125

Aging Schedule:

14 days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance		Chemical Analysis		
	Oil Color Change (ASTM)	Other Visual Changes	GC	F Ion (ug)	%R-125 Reacted Oil Analysis
150°C	From 2.5 to 3.0	Steel: No change	No change	8.2	0.005
175°C	From 2.5 to 3.0	Steel: No change	No change	7.7	0.005
200°C	From 2.5 to 3.0	Steel: No change	No change	7.7	0.005

FIGURE A-15

Tube CH-01
R-125/PE Ester (branched acid)
14 Days @ 150°C

RUN 0 9 MAR/04/92 09:52:28

RT	AREA	TYPE	NR/HT	AREA%
0.33	3291	BB	0.051	0.221
0.86	1483400	FB	0.100	99.779
1.25	0	BB	0.000	0.000

TOTAL AREA= 1486700
MUL FACTOR= 1.0000E+00

RT	AREA	TYPE	NR/HT	AREA%
0.34	3595	BB	0.050	0.106
0.83	3390200	FB	0.117	99.894
1.25	0	BB	0.000	0.000

TOTAL AREA= 3393800
MUL FACTOR= 1.0000E+00

Table A-13: STABILITY of R-134a with PENTAERYTHRITOL
ESTER (Branched Acid)

Sealed Tube Contents:

Valve steel strip
1.0 cc (1.0 g) of Castrol SW32
1.0 g of R-134a

Aging Schedule:

14 Days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance		Chemical Analysis			
	Oil Color Change (ASTM)	Other Visual Changes	GC	F Ion (ug)	%R-134a Reacted	Oil Analysis
150°C	From 2.5 to 3.0	Steel: No change	No change	2.5	0.001	
175°C	From 2.5 to 3.0	Steel: No change	No change	1.4	0.001	
200°C	From 2.5 to					

FIGURE A-25

RUN # 13 MAR/04/92 11:18:47

AREA%	RT	AREA TYPE	OR/INT	AREA%
0.34	1303	BB	0.052	0.073
1.10	1007700	PB	0.120	99.927

TOTAL AREA= 1009100
MUL FACTOR= 1.0000E+00

RUN # 11 JAN/16/92 14:02:49

AREA%	RT	AREA TYPE	OR/INT	AREA%
0.34	1012	BB	0.052	0.065
1.07	2000200	PB	0.140	99.935

TOTAL AREA= 2002000
MUL FACTOR= 1.0000E+00

Table A-14: STABILITY of R-134a with PENTAERYTHRITOL
ESTER (100 cst)

Sealed Tube Contents:

Valve steel strip
1.0 cc (1.0 g) of Emery 2928 ISO 100
1.0 g of R-134a

Aging Schedule:

14 Days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance		Chemical Analysis			
	Oil Color Change (ASTM)	Other Visual Changes	GC	F Ion (ug)	%R-134a Reacted	Oil Analysis
150°C	No change at 3.0	Steel: No change	No change	1.6	0.001	
175°C	From 3.0 to 3.5	Steel: Darkened	No change	1.0	0.001	
200°C	From 3.0 to					

FIGURE A-27

STOP

RUN 0 11

JAN/16/92 14:02:49

AREA%	RI	AREA TYPE	OR/HT	AREA%
0.34	1012	BB	0.052	0.053
1.07	2000200	PD	0.140	99.935

TOTAL AREA= 2000200
 MUL FACTOR= 1.0000E+00

RUN 0 15

JAN/04/92 13:32:23

AREA%	RI	AREA TYPE	OR/HT	AREA%
0.34	1014	BB	0.051	0.053
1.19	1049000	PD	0.120	99.945

TOTAL AREA= 1050000
 MUL FACTOR= 1.0000E+00

Table A-15: STABILITY of R-142b with ALKYL BENZENE OIL

Sealed Tube Contents:

Valve steel strip
1.0 cc (0.9 g) of Zerol 150
0.9 g of R-142b

Aging Schedule:

14 days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance of Aged Tubes		Chemical Analysis		
	Color Change of Oil (ASTM)	Other Visual Observations	GC	Cl Ion (ug)	%R-142b Reacted
150°C	No change at 2.0	Steel: No change	No change	34.8	0.011
175°C	From 2.0 to 2.5	Steel: No change	No change	45.0	0.014
200°C	From 2.0 to				

FIGURE A-29

R-142b "As Received"

RUN # 5 FEB/19/92 09:40:32

RT	AREA	TYPE	NR/HT	AREA%
0.34	1709	BP	0.050	0.047
0.49	873	PB	0.049	0.024
1.35	2886	BB	0.128	0.079
2.54	3659400	PB	0.355	99.851

TOTAL AREA= 3664900
MUL FACTOR= 1.0000E+00

Tube CO-02 R-142b/Alkylbenzene

14 Days @ 150°C

RUN # 9 MAR/18/92 14:45:31

RT	AREA	TYPE	NR/HT	AREA%
0.34	1507	BP	0.052	0.082
0.48	403	PB	0.049	0.022
2.65	1829700	PB	0.313	99.896

TOTAL AREA= 1831600
MUL FACTOR= 1.0000E+00

Table A-16: STABILITY of R-143a with PENTAERYTHRITOL
ESTER (Branched Acid)

Sealed Tube Contents:

Valve steel strip
1.0 cc (1.0 g) of Castrol SW32
1.0 g of R-143a

Aging Schedule:

14 Days at temperatures shown

Test Results:

Aging Temp.	Visual Appearance		Chemical Analysis			
	Oil Color Change (ASTM)	Other Visual Changes	GC	F Ion (ug)	%R-143a Reacted	Oil Analysis
150°C	From 2.5 to 3.0	Steel: No change	No change	7.9	0.003	
175°C	From 2.5 to 3.0	Steel: No change	No change	4.1	0.002	
200°C	From 2.5 to					

FIGURE A-31

R-143a "As Received"

RUN 0 1 FEB/19/92 08:44:18

RT	AREA	TYPE	NR/HIT	AREA%
0.34	1611	BP	0.049	0.052
0.49	1064	PB	0.057	0.035
0.85	3070100	PB	0.114	99.913

TOTAL AREA= 3072000
MUL FACTOR= 1.0000E+00

Tube CP-02

R-143a/PE Ester (branched acid)

RUN 0 7 MAR/18/92 13:46:21

RT	AREA	TYPE	NR/HIT	AREA%
0.33	1674	BP	0.051	0.002
0.48	757	PB	0.049	0.037
0.86	2050000	PB	0.103	99.892

TOTAL AREA= 2052400
MUL FACTOR= 1.0000E+00

**DATE
FILMED
7/20/92**