**DOE/PC/79921-T11
(DE92009916)**

**PORE STRUCTURE AND REACTIVITY CHANGES IN HOT COAL GAS
DESULFURIZATION SORBENTS**

Final Report for the Period September 1987—January 1991

**By
Stratis V. Sotirchos**

May 1991

Work Performed Under Contract No. FG22-87PC79921

**For
U.S. Department of Energy
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania**

**By
University of Rochester
Rochester, New York**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report has been reproduced directly from the best available copy.

Available to DOE and DOE contractors from the Office of Scientific and Technical Information, P.O. Box 62, Oak Ridge, TN 37831; prices available from (615)576-8401, ~~DDO-606-8401~~.

Available to the public from the National Technical Information Service, U. S. Department of Commerce, 5285 Port Royal Rd., Springfield, VA 22161.

**Pore Structure and Reactivity Changes in Hot Coal Gas
Desulfurization Sorbents**

Final Report

September 1987 - January 1991

Prepared by:

Prof. Stratis V. Sotirchos

May 1991

Work Performed under Grant No.: DE-FG22-87PC79921

Performed for:

U.S. Dept. of Energy
University Coal Research Program
Pittsburgh Energy Technology Center
Pittsburgh, Pennsylvania

Performed at:

University of Rochester
Dept. of Chemical Engineering
Rochester, NY 14627

EXECUTIVE SUMMARY

The primary objective of the project was the investigation of the pore structure and reactivity changes occurring in metal/metal oxide sorbents used for desulfurization of hot coal gas during sulfidation and regeneration, with particular emphasis placed on the effects of these changes on the sorptive capacity and efficiency of the sorbents. Commercially available zinc oxide sorbents were used as model solids in our experimental investigation of the sulfidation and regeneration processes.

The sulfidation of porous zinc oxide in hydrogen sulfide-nitrogen mixtures was studied in a thermogravimetric analysis system. Experiments were carried out with particles in the range of 52-350 μm , at temperatures from 300 to 600°C, and with different hydrogen sulfide concentrations. The analysis of the experimental results showed that the sulfidation reaction was of first order with respect to the H_2S concentration, and that the conversion vs. time trajectories depended strongly on the particle size. The generalized pore model of Yu and Sotirchos (1987), a detailed model for diffusion, reaction, and structure evolution in chemically reacting porous media, was used to analyze the experimental data, and good agreement between model and experiment was observed. The intraparticle diffusional limitations and their evolution with the progress of the reaction were found to be the factor influencing most the sorptive capacity of the ZnO sorbent for H_2S removal.

By using two commercially available ZnO sorbents differing in porosity and pore size distribution, we were able to experimentally investigate the effects of pore structure on the performance of metal oxide sorbents during H_2S removal from coal gas at high temperatures. The pore structure of fresh, heat-treated, sulfided, and regenerated sorbents was analyzed by mercury porosimetry and nitrogen adsorption using samples prepared in a fluidized- or a fixed-bed reactor under conditions similar to those used in the thermogravimetric analysis system. Strong effects of the pore structure of the sorbents on their performance during desulfurization were revealed by our reactivity and structure evolution data. The analysis of the experimental data showed that differences in the performance

of sorbents of the same metal oxide can be explained on the basis of their different morphological characteristics provided that an appropriate model for diffusion, reaction, and structure evolution in the interior of the reacting sorbent particles is employed.

We also worked on the theoretical investigation of the transport, reaction, and pore structure evolution phenomena that are encountered in the sulfidation and regeneration processes. We modified a mathematical model that was developed in past studies by our research group (Yu and Sotirchos, 1987) so that it can be used to describe cyclic sulfidation and regeneration. We investigated the problem of multicomponent diffusion and convection of gases in porous media of pore network structure. Finally, we developed a detailed mathematical model for fixed-bed desulfurization reactors, in which structural models of distributed pore or grain size, which can describe almost all phenomena encountered in gas-solid reactions with solid product, were used to simulate the evolution of the internal structure of the porous metal oxide in the course of its reaction with H_2S . The fixed-bed desulfurization model was used to study the transient behavior of desulfurization reactors loaded with zinc oxide pellets. The results of our computations showed that the form of the pore or grain size distribution strongly influences the transient behavior of the desulfurization reactor and, consequently, its breakthrough time and sorbent utilization, even for the same values of initial internal surface area and porosity.

TABLE OF CONTENTS

EXECUTIVE SUMMARY	ii
TABLE OF CONTENTS	iv
LIST OF FIGURES	vi
LIST OF TABLES	x
1. BACKGROUND STATEMENT	1
2. REACTIVITY EVOLUTION DURING SULFIDATION OF POROUS ZINC OXIDE	5
2.1. Introduction	5
2.2. Materials	8
2.3. Test Studies	12
2.4. Experimental Results	14
2.5. Analysis of the Experimental Data and Discussion	18
2.6. Summary and Conclusions	32
2.7. Notation	33
3. EFFECTS OF PORE STRUCTURE ON THE PERFORMANCE OF COAL GAS DESULFURIZATION SORBENTS	35
3.1. Introduction	35
3.2. Materials	37
3.3. Pore Structure Characterization Results	39
3.4. Reactivity Results	50

3.5. Analysis of the Experimental Data	55
3.6. Summary	68
4. EXPERIMENTAL AND THEORETICAL INVESTIGATION OF THE REGENERATION OF SULFIDED SORBENTS	70
4.1. Introduction	70
4.2. Materials and Pore Structure Data	73
4.3. Experimental Reactivity Results	75
4.4. Model Predictions and Discussion	83
4.5. Summary	92
5. DEVELOPMENT OF A MATHEMATICAL MODEL FOR FIXED-BED DESULFURIZATION REACTORS	94
5.1. Introduction	94
5.2. Development of the Mathematical Model	94
5.3. Computational Procedure	106
5.4. Application to ZnO Sulfidation	106
5.5. Summary	118
5.6. Notation	119
BIBLIOGRAPHY	121
 APPENDIX: Sotirchos, S.V., 1989, Multicomponent Diffusion and Convection in Pore Networks, AIChE J., 35, 1953. (Reprint Removed)	

LIST OF FIGURES

Figure		Page
2.1.	Mercury penetration volume vs. pore radius for particles and pellets.	7
2.2.	Porosity distribution density functions for particles and pellets.	7
2.3.	Apparatus for reactivity measurements.	9
2.4.	Percentage of H_2S in the exit stream of the reactor.	11
2.5.	Effects of pan materials on conversion vs. time curves.	11
2.6.	Particle size and flow direction effects on the reactivity evolution data.	13
2.7.	Conversion vs. normalized time results at $600^\circ C$ and gas flow from below.	15
2.8.	Conversion vs. normalized time results at $500^\circ C$ and gas flow from below.	15
2.9.	Temperature dependence of the reactivity of $53-62\ \mu m$ particles for flow from above.	16
2.10.	Temperature dependence of the reactivity of $297-350\ \mu m$ particles for flow from above.	16
2.11.	Model predictions vs. the experimental data at $600^\circ C$ with 0.5% H_2S .	22
2.12.	Model predictions vs. the experimental data at $500^\circ C$ with 0.5% H_2S .	22
2.13.	Model predictions vs. the experimental data at $400^\circ C$ with 0.5% H_2S .	23
2.14.	Model predictions vs. the experimental data at $300^\circ C$ with 0.5% H_2S .	23
2.15.	Effect of heat treatment under nitrogen on sorbent reacted at $300^\circ C$.	25
2.16.	Model predictions vs. the experimental data at $600^\circ C$ with 0.5% H_2S .	27
2.17.	Model predictions vs. the experimental data at $600^\circ C$ with 0.5% H_2S .	27

2.18.	Variation of the effective diffusivity with the conversion for different models at 600°C.	29
2.19.	Model predictions vs. the experimental data at 600°C with 0.5% H_2S for variable tortuosity.	29
2.20.	Effect of coordination number on the model predictions.	31
2.21.	Effect of diffusivity in the product layer on the model predictions for $z = \infty$.	31
3.1.	Pore size distributions of the unreacted zinc oxide sorbents.	38
3.2.	Nitrogen isotherm of the heat-treated sorbent G-72D and its sulfide.	41
3.3.	Nitrogen isotherm of the heat-treated sorbent C7-2 and its sulfide.	41
3.4.	Cumulative pore volumes of heat-treated sorbents computed from the mercury porosimetry and the nitrogen adsorption and desorption data.	43
3.5.	Primary and secondary mercury intrusion-extrusion data for the heat-treated C7-2 sample.	47
3.6.	Primary and secondary mercury intrusion-extrusion data for the heat-treated G-72D sample.	47
3.7.	Mercury intrusion-extrusion data for fully sulfided G-72D and C7-2 sorbents.	48
3.8.	Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for different particle sizes sulfided at 400°C with 0.5% H_2S .	52
3.9.	Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for particles of 53-62 and 297-350 μm , sulfided at 500°C with 0.5% H_2S .	52
3.10.	Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for particles of 53-62 and 297-350 μm , sulfided at 600°C with 0.5% H_2S .	53
3.11.	Experimental data for 53-62 μm particles of sorbent C7-2 reacted with various H_2S-N_2 mixtures at 600°C.	53
3.12.	Experimental data for 297-350 μm particles of sorbent C7-2 reacted with various H_2S-N_2 mixtures at 600°C.	54
3.13.	Conversion vs. normalized time curves for sulfidation of sorbent C7-2 at 600°C.	54

3.14.	Comparison of the generalized random pore model predictions with the experimental data at 600°C for samples C7-2 and G-72D.	58
3.15.	Comparison of the generalized random pore model predictions with the experimental data at 500°C for sample C7-2.	58
3.16.	Comparison of the generalized random pore model predictions with the experimental data at 400°C for sample C7-2.	59
3.17.	Evolution of the effective diffusivity of sorbents C7-2 and G-72D at 600°C with the progress of sulfidation.	64
3.18.	Comparison of the pore size distributions obtained from the mercury porosimetry data of sample C7-2 sulfided at various conversions with the predicted by the mathematical model pore size distributions at the same conversions.	66
3.19.	The mathematical model predictions for the conversion profiles in 297-350 μm particles at 50% average conversion for sorbents C7-2 and G-72D.	66
3.20.	Sulfur and zinc maps obtained from the SEM/EDS analysis of 297-350 μm particles of sorbents C7-2 and G-72D at 50% average conversion.	67
4.1.	Mercury porosimetry data for unreacted (heat-treated) and regenerated sorbents.	74
4.2.	Nitrogen isotherms for unreacted (heat-treated) and regenerated sorbents.	74
4.3.	Multiple sulfidation-regeneration experiments for 53-62 μm particles of sorbent G-72D.	77
4.4.	Multiple sulfidation-regeneration experiments for 297-350 μm particles of sorbent G-72D.	77
4.5.	Multiple sulfidation-regeneration experiments for 53-62 μm particles of sorbent C7-2.	80
4.6.	Multiple sulfidation-regeneration experiments for 297-350 μm particles of sorbent C7-2.	80
4.7.	Comparison of the conversion vs. time regeneration data for 297-350 μm of sample C7-2 using different O_2 concentrations.	82
4.8.	Two dimensional analog of pore structure evolution during sulfidation and regeneration.	85
4.9.	Conversion vs. time data for sulfidation of 53-62 μm unreacted and regenerated particles of sorbent G-72D.	86
4.10.	Conversion vs. time data for sulfidation of 297-350 μm unreacted and regenerated particles of sorbent G-72D.	86

4.11.	Comparison of the sulfidation data for 53-62 μm particles of sample C7-2 with the model predictions.	88
4.12.	Comparison of the sulfidation data for 297-350 μm particles of sample C7-2 with the model predictions.	88
4.13.	Comparison of the experimental data of sample C7-2 for the first two sulfidation cycles with the model predictions.	90
4.14.	Comparison of the regeneration data for 53-62 μm particles of sample C7-2 with the model predictions.	91
4.15.	Comparison of the regeneration data for 297-350 μm particles of sample C7-2 with the model predictions.	91
5.1.	Computer-generated section (1 μm in side) of a random pore structure with discrete bimodal distribution of pore size.	102
5.2.	Effects of pseudosteady state assumption for the gaseous species in the interior of the pellets.	107
5.3.	Breakthrough curves for solids with discrete pore size distribution (unimodal or bimodal) of the same porosity and internal surface area.	107
5.4.	Sorbent utilization results for the solids of Fig. 5.3. for 10 ppm breakthrough concentration.	108
5.5.	Variation of the effective diffusivity in the pellets of Fig. 5.3 with the local conversion.	108
5.6.	Variation of the volumetric reaction rate constant in the pellets of Fig. 5.3 with the local conversion.	110
5.7.	Variation of the average volumetric reaction rate constant in the pellets of Fig. 5.3 with the local conversion in the bed.	110
5.8.	Breakthrough curves for solids with discrete pore size distribution (unimodal or bimodal).	113
5.9.	Concentration and conversion profiles in the reactor for solid B of Fig. 5.3.	113
5.10.	Breakthrough curves for solids with discrete grain size distribution (unimodal or bimodal) of the same porosity and internal surface area.	116
5.11.	Variation of the volumetric reaction rate constant in the pellets of Fig. 5.10 with the local conversion.	116

LIST OF TABLES

Table		Page
2.1.	Initial reaction rates, effective diffusivities, effectiveness factors, and reaction rate constants with and without correction for intraparticle diffusion.	20
3.1.	Skeletal densities of the unreacted (heat-treated) and fully sulfided sorbents.	39
3.2.	Analysis of the nitrogen isotherm data of the sorbents and their sulfides.	42
3.3.	Data for the application of the generalized random pore model.	56
3.4.	Diffusion coefficients in the product layer and reaction rate constants used in the application of the generalized random pore model.	60
4.1.	Physical properties of sample C7-2, reaction conditions, and parameters used in the application of the mathematical model.	89
5.1.	Physical, kinetic, reactor, and fixed-bed data used for ZnO .	109

1. BACKGROUND STATEMENT

Several sulfur-containing compounds, predominantly H_2S , are formed during coal gas production through coal gasification. Owing to their toxicity and a number of other undesirable properties, direct utilization of the produced coal gas is impossible without first reducing its sulfur content to environmentally and operationally acceptable levels. Among various problems associated with H_2S and other sulfur-containing compounds, one can mention catalyst poisoning (if the coal gas is used as synthesis gas), corrosion, and SO_2 formation during coal gas combustion. The level to which the sulfur content of the coal gas must be reduced by desulfurization depends on the process for which the coal gas is needed. For instance, if the fuel gas is going to be used in molten-carbonate fuel-cell power plants, its sulfur level must be brought down to about 1 ppm or less for successful cell operation (Jalan, 1983). Among the various desulfurization methods developed to date, the most advantageous ones appear to be those operating at high temperatures, mainly because of the fact that they involve negligible loss of sensible heat of the fuel gas. This leads to considerable improvement of the thermal efficiency of the overall process if the fuel gas is to be used following desulfurization in a high temperature process.

Hot coal gas desulfurization processes are based on the capacity of various metal/metal oxide solids to react with hydrogen sulfide and other sulfur containing compounds to form metal sulfides. The economic feasibility of a given metal/metal oxide sorbent largely depends on its regeneration characteristics. For most metal/metal oxide solids, regeneration is carried out by heating the spent sorbent (metal sulfide) in air or air/steam mixtures. An economically feasible desulfurization sorbent should not only be regenerable but also retain its original sulfur capture capacity over a number of absorptive/regenerative cycles. Various supported (on ceramic support) or unsupported metal/metal oxide sorbents have been studied experimentally for hot gas desulfurization, such as iron oxides, zinc oxide, copper/copper oxides, nickel, and cobalt titanate (e.g., see studies by Gibson and Harrison (1980), Tamhankar et al., (1981), Ranade and Harrison (1981), Jalan (1983), and Anderson et al. (1984)). Iron oxide, zinc oxide, and copper/copper oxide based systems have attracted the most interest as they appear to be the most promising ones.

Both the sulfur absorption and sorbent regeneration steps are noncatalytic gas-solid

reactions characterized by formation of a solid product. The solids used in hot gas desulfurization are highly porous, and consequently reaction mainly occurs in the interior of the solid pellets at the interface between solid reactant and solid product. Because of the formation of the solid product, a number of processes must be considered in the development of single-pellet models for the above gas-solid systems and in the analysis of obtained experimental data, in addition to intraparticle diffusion and reaction. The internal structure of the reacting solid, for instance, must be described by two temporally and spatially evolving surfaces, the reaction surface (solid reactant-solid product interface) and the pore surface. Moreover, because of slow diffusion of the reactive species in the product layer, large concentration gradients may be present in the product layer even if appreciable concentration gradients do not exist in the porous structure.

The presence of the solid product may lead to additional complications if the ratio of stoichiometrically equivalent volumes of solid reactant and solid product is greater than one, as it appears to be the case with most metal oxide sorbents used in hot gas desulfurization. Since the solid product occupies more space than the solid from which it results, the porosity diminishes with the progress of the reaction, and incomplete conversion and pore plugging phenomena might be observed. Under conditions of significant concentration gradients in the interior of the reacting particles or pellets, pore closure may first occur at the external surface area preventing further penetration of the reactive gases and subsequent reaction in the interior. Another phenomenon that may take place in noncatalytic gas-solid systems exhibiting pore closure behavior is the formation of inaccessible pore space. This situation results when the feeder pores of a finite cluster of pores are filled with solid product. Such phenomena have been predicted by generalized pore and grain structural models were developed recently by our research group (Sotirchos and Yu, 1985 and 1988; Yu and Sotirchos, 1987) for application to gas-solid reactions with or without pore closure behavior. The predictions of our mathematical models were verified by carrying out reactivity experiments on the reaction of calcined limestone with SO_2 (Yu, 1987).

The above observations are directly applicable to hot gas desulfurization sorbents since they may also exhibit pore closure behavior. Moreover, several experimental studies

revealed strong effects of pellet size on the sorptive capacity of desulfurization sorbents (e.g., Jalan (1983) for the CuO/ZnO sorbent) suggesting that the process occurs under conditions of significant intraparticle concentration gradients. Nevertheless, although a good deal of experimental effort has been put into investigating the reactivity and capacity of various metal/metal oxide sorbents for sulfur compound removal from coal gas, limited work has been done on the characterization of these sorbents (in terms of their pore size distribution, intraparticle diffusivity, etc.) with the progress of their conversion. The few structural studies that have been presented in the literature (e.g., Caillet and Harrison (1982)) include only surface area vs. time (or conversion) data, which alone are insufficient for developing and testing design models for desulfurization reactors.

In view of the above observations, a research program was proposed for the study of the evolution of the reactivity, intraparticle diffusivity, and pore size distribution of metal/metal oxide based sorbents used for coal gas desulfurization with the extent of solid conversion and sorbent use (repeated adsorption/regeneration cycles). Zinc oxide is among the most frequently used metal oxides in desulfurization studies, either as a single oxide or as a mixture with other metal oxides, since the sulfidation of ZnO leads to low (of the order of a few *ppm* or less) concentrations of H_2S at the exit of fixed-bed reactors. On the other hand, the chemistry of zinc oxide sulfidation and regeneration is relatively simple, and thus, it is easier to differentiate between the effects of the kinetics of the reaction and of those of the internal pore structure on the performance of ZnO sorbents. It was therefore decided to use commercially available ZnO sorbents in most of the experiments performed in this work.

Two ZnO sorbents differing in initial pore structure (porosity, surface area, and pore size distribution) were sulfided and regenerated under reaction conditions where sintering and zinc loss do not take place (i.e., temperatures lower than $650^\circ C$). Reactivity evolution experiments were carried out in a thermogravimetric analysis system (TGA) over relatively broad ranges of particle size, reaction temperature, and H_2S concentration. The pore structure of the solids used in the reactivity experiments (surface area, pore volume, and pore size distribution) was characterized by gas adsorption and mercury porosimetry. Samples of fresh, heat-treated with nitrogen at high temperatures, sulfided,

and regenerated sorbents were prepared in fixed-bed and fluidized-bed reactors under reaction conditions similar to those used in the thermogravimetric experiments. The mercury porosimetry pore size distributions were compared with those obtained by the analysis of the gas adsorption and desorption data. The generalized random pore model of Yu and Sotirchos (1987), a detailed mathematical model that describes most of the phenomena encountered in gas-solid reactions with solid product formation was used to analyze the reactivity evolution data obtained in our TGA studies.

In this report, we present and discuss the most important experimental results that we obtained on the evolution of reactivity during sulfidation of ZnO sorbents (Section 2), the effects of pore structure on the sorptive capacity of ZnO sorbents (Section 3), and the effects of pore structure and operating conditions on the regeneration of ZnO sorbents (Section 4). We also describe (Section 5) a detailed model for fixed-bed desulfurization reactors and discuss its application to ZnO sulfidation. Finally, in a research article attached as an appendix to this report, we carry out an analysis of the problem of multicomponent diffusion and convection of gases in porous solids, which is encountered whenever a rigorous treatment of the transport processes during gas-solid reactions – such sorbent regeneration and sulfidation – is attempted. Each section in the report is to a large degree self-contained in the sense that the material presented and discussed there can be followed and understood independently of the results presented in the other sections.

2. REACTIVITY EVOLUTION DURING SULFIDATION OF POROUS ZINC OXIDE

2.1. Introduction

The gasification of coal leads to formation of sulfur-containing species, like H_2S , COS and SO_2 , and it is thus necessary to remove these corrosive compounds prior to using the produced coal gas. The level to which the sulfur content of the coal gas must be reduced depends both on environmental regulations and on the application for which the coal gas is intended. For instance, if the coal gas is going to be burned downstream for power production, its sulfur content should be low to keep SO_2 emissions within acceptable limits. On the other hand, if the fuel gas is going to be used in molten-carbonate fuel cells, its sulfur level should be brought down to about 1 ppm for problem-free cell operation (Jalan, 1983). Similarly, if the coal gas is intended to be used as synthesis gas, its sulfur content should be reduced to prevent or delay poisoning of the catalysts used in synthesis reactions.

Desulfurization of hot coal gas at low temperatures (around $100^\circ C$) causes loss of most of its sensible heat content. This energy loss can be avoided by using porous solids (mostly metal oxides) to remove the sulfur-containing species (primarily H_2S) at high temperatures. The reaction of hydrogen sulfide with a metal oxide can generally be described as follows:

Candidate sorbents are usually evaluated on the basis of the following criteria: the equilibrium concentration of the hydrogen sulfide at the process conditions, the reaction rate during sulfidation and regeneration, the sorbent utilization after different sulfidation/ regeneration cycles and the mechanical properties of the solid (strength and resistance to attrition).

Several experimental or theoretical studies have been carried out to evaluate the comparative performance of single and mixed metal oxides under typical reaction conditions in desulfurization units, but, the conclusions reached in each study depend strongly on the criteria used for evaluation. Detailed thermodynamic analyses of reaction (1) for

various oxides have been carried out by Westmoreland and Harrison (1976) and Furimsky and Yumura (1986). Kinetic studies, on the other hand, have been carried out, among others, by Westmoreland et al. (1977) in a thermogravimetric analysis (TGA) reactor, Yumura and Furimsky (1985) and Tamhankar et al. (1986) in fixed-bed arrangements, and Lew et al. (1989) in both TGA and fixed-bed arrangements using the same material.

Zinc oxide is among the most frequently used oxides in desulfurization studies, either as a single oxide or as a mixture with other metal oxides, since the sulfidation of ZnO leads to low (of the order of a few ppm or less) concentrations of H_2S at the exit of fixed-bed reactors. Actually in some cases where mixed oxides were used (Tamhankar et al., 1986; Lew et al., 1989), exit concentrations lower than the value computed from the equilibrium of reaction (1) for ZnO or the other oxides in the mixture were measured. However, there are a few drawbacks in the use of ZnO in desulfurization units: Under the reducing atmosphere of the hot coal gas stream, reduction of the oxide may take place at relatively high temperatures ($> 600^\circ C$) and lead to vaporization of zinc and, therefore, loss of a portion of the sorbent after extended operation or after a number of sulfidation/regeneration cycles. Sintering of the porous material may occur at temperatures above $700^\circ C$ (Ranade and Harrison, 1981; Gangwal et al., 1989). Finally, formation of zinc sulfate may take place during regeneration and thermal treatment at high temperatures may be required to decompose the sulfide to ZnO (Krishnan et al., 1985). According to Lew et al. (1989), these drawbacks can be alleviated or even eliminated by use of zinc titanate sorbents, which exhibit both high H_2S removal efficiency and low sulfur concentrations at the exit of the reactor, similar to those seen for pure ZnO sorbents.

The sulfidation of zinc oxide (ZnO) is a noncatalytic gas-solid reaction characterized by formation of a solid product (ZnS). There are thus several transport mechanisms (in the product layer and in the pore space) that must be considered in the analysis and interpretation of experimental data for this reaction. Moreover, the solid product occupies more space than the solid reactant, and consequently, the porosity diminishes in the course of the reaction and pore surface area is lost as the small pores are getting plugged with solid product. Simple mathematical models are usually used to analyze experimental data for the $ZnO-H_2S$ reaction and other sulfidation reactions. For instance, Focht et al.

Figure 2.1. Mercury penetration volume vs. pore radius for particles and pellets.

Figure 2.2. Porosity distribution density functions for particles and pellets.

(1988) used a shrinking-core model to interpret their experimental data, while a modified grain model, allowing for sintering effects was used by Ranade and Harrison (1981). Good agreement is usually obtained between the predictions of the various simple models and experimental reactivity evolution (conversion vs. time) data, but at the expense of letting most of the parameters of the process vary with the operating conditions and in this way compromising the predictive capabilities, if any, of these models.

The reaction of a porous ZnO sorbent with H_2S , under reaction conditions where sintering and zinc loss do not take place, was investigated in this study. Reactivity evolution experiments were carried out in a thermogravimetric analysis reactor over relatively broad ranges of particle size, reaction temperature and H_2S concentration. The structure of the unreacted solid was characterized by gas adsorption and mercury porosimetry. The experimental data were analyzed with the generalized random pore model of Yu and Sotirchos (1987). This model can describe most phenomena encountered in gas-solid reactions with solid product formation (such as the sulfidation of metal oxides), including formation of inaccessible pore space.

2.2. Materials and Experimental Procedures

A commercially available zinc oxide sorbent supplied by United Catalysts Inc. (Catalyst G-72D), was used in our experiments. The sorbent was treated at $600^\circ C$ under nitrogen for 30 min before every sulfidation experiment. About 6% of the sorbent, on a weight basis, was lost during this treatment, probably because of loss of binder material and humidity. Chemical analysis of the treated sorbent, performed by X-Ray Assay Laboratories Ltd., showed that the sample consisted of 89.3% ZnO , 1.5% CaO , 6.6% Al_2O_3 , and 2.6% MgO . The sorbent extrusions were crushed, and sieving was used to isolate the following particle sizes from the crushed material: 53-62, 88-105, 210-250 and 297-350 μm . The reactive gas consisted of 10500 ppm H_2S in N_2 and was diluted to the desired concentration by mixing with more N_2 . High purity gases were used in all experiments.

The pore size distribution of the sorbent was determined by mercury porosimetry, done using a Micromeritics Autopore 9220 II mercury porosimeter. In order to ascertain that the pore size distribution remained the same after fragmentation of the solid, mercury

Figure 2.3. Apparatus for reactivity measurements.

porosimetry analysis were performed both for pellets and particles. The obtained mercury intrusion curves are shown in Fig. 2.1. It is seen that the mercury intrusion curve for the fresh (untreated) pellet has the same shape for interstices smaller than $10\ \mu\text{m}$ as that for the fresh particles. This is shown more clearly in Fig. 2.2 which presents the porosity density functions that were computed using the intrusion results of Fig. 2.1 and assuming a structure of long cylindrical capillaries. The initial rise of the intrusion curve of the particles (for pore diameters greater than $10\ \mu\text{m}$) corresponds to mercury invading the interparticle space of the sample. Heat treatment shifted the pore size distribution towards larger pore sizes (Fig. 2.2), and caused a small increase in the total porosity (Fig. 2.1). Specifically, the most probable radius increased from about 90 to 125 Å, while the porosity increased from about 48 to 53%.

The BET surface area was found to be equal to $27.7\ \text{m}^2/\text{g}$, while the pore size distribution extracted from the mercury porosimetry data gave (for pores greater than 60 Å) $32\ \text{m}^2/\text{g}$. (The mercury porosimetry data for pores with diameters less than 60 Å were ignored since they usually contain significant errors due to sample or mercury compressibility.) It is not surprising that the surface areas obtained from the two methods are different. When a perfectly interconnected pore network is used to interpret mercury porosimetry data, pore space that may belong to large pores or cavities is attributed to the smaller feeder pores through which it is invaded by mercury, thus leading to overestimation of the total surface area.

The change of the sorbent weight during sulfidation was measured using the thermogravimetric analysis system of Fig. 2.3. The system is based on a Cahn 2000 electrobalance. To prevent corrosion of the mechanism of the instrument by H_2S , the balance jar was purged at all times with nitrogen. Depending on the direction of the reactive gas flow in the reactor tube, the purge stream left the system either without reaching the sample pan (upward flow) or after being mixed with the reactive gas. The sorbent was uniformly spread on a circular pan hang from the sample arm of the microbalance with thin platinum wire. The initial and the final weight of the reactant solid were measured at the start and end of each experiment at ambient conditions and with no gas flow in the reactor. Conversion vs. time curves were constructed from the thermogravimetric data

Figure 2.4. Percentage of H_2S in the exit stream of the reactor. (0.5% H_2S , 200 ml/min, 600°C, 2 mg initial sample weight and flow from above. Patrick et al. (1989) used $CuO-Al_2O_3$, 88-105 μm particles, 30 mg initial sample weight, 4.2% H_2S , and 80 ml/min.)

Figure 2.5. Effects of pan materials on conversion vs. time curves (600°C, 0.5% H_2S , 297-350 μm particles, and flow from below).

by attributing the observed weight gain of the heat-treated sorbent to the formation of zinc sulfide. The reaction temperature was measured using a K-type thermocouple in a ceramic sheath, positioned close to the pan. All experiments were carried out at constant temperature.

2.3. Test Studies

Preliminary sulfidation experiments were carried out to investigate the dependence of the reactivity data on the sample size and the flow rate of the reactive gas. It was found that combinations of samples of less than 3 mg and flow rates of more than 50 ml/min did not give significantly different conversion vs. time results. Larger samples and smaller flow rates influenced strongly the obtained reaction trajectories even if all other reaction conditions remained the same. Based on these results, it was decided to use initial sorbent weights of the order of 2 mg and 200 ml/min flow rates in all of our experiments.

Large samples cannot be spread as a thin layer on the pan and might lead to significant interparticle diffusional limitations, which may intensify with the progress of the reaction, especially if formation of solid product causes particle agglomeration. Large samples in combination with small flow rates can also lead to nondifferential operation of the TGA reactor. Fig. 2.4 gives the fraction of H_2S that leaves the reactor unreacted as a function of time, estimated by performing a mass balance on H_2S , for experiments done in this study at 600°C, 200 ml/min flow rate, 0.5% H_2S , and 2 mg of sorbent for various particle sizes. It is seen that under these reaction conditions, the H_2S concentration at the exit of the reactor is about 10% lower than that at the inlet during the initial stages of the reaction. Our analysis of reactivity evolution results reported in the literature for other sulfidation reactions showed that much lower relative exit concentrations of H_2S were present in some of the reported experimental results. For instance, our calculations showed (see Fig. 2.4) that in a study of the reaction of H_2S with a $CuO-Al_2O_3$ sorbent by Patrick et al. (1989), the H_2S fraction leaving the thermogravimetric reactor was initially only 67% of that entering it at the conditions of one of their experiments (30 mg, 80 ml/min, 600°C, and 4.2% H_2S).

We studied the effects of the pan material on the experimental data by using plat-

Figure 2.6. Particle size and flow direction effects on the reactivity evolution data (600°C and 0.5% H_2S).

inum, gold, and quartz sample holders of the same size and shape in the TGA reactor. When an empty platinum pan was exposed to the H_2S mixture, there was a small weight gain, which increased with the temperature in the reactor. This phenomenon could be due to chemisorption of sulfur by platinum and to formation of platinum sulfides (Bartholomew et al., 1982). Interaction between the platinum pan and the reactant mixture was also noticed by Gibson (1977) as change in the pan color during sulfidation, while Patrick et al. (1989) reported that platinum catalyzed the decomposition of H_2S to elemental sulfur. A similar, but much smaller, uptake during a blank experiment was observed for the gold pan. We corrected the conversion vs. time trajectories obtained with metal pans by subtracting from the total weight change vs. time data the weight vs. time results of the blank experiment. The comparison of experimental data with different pan materials is shown in Fig. 2.5 for particles of 297-350 μm , reacted at $600^\circ C$ with 0.5% H_2S and flow upward. It is seen that the experimental curves obtained using metal pans are similar to that for the quartz pan, where no correction was required. Nevertheless, it was decided to use quartz pans in our experiments and thus avoid having to correct the weight vs. time data.

The reaction trajectories were found to be influenced by the direction of flow in the TGA reactor. Experiments with flow from above, that is, with the particles directly exposed to the flowing gas stream, gave higher, in general, conversions, suggesting larger mass transfer coefficients than experiments with flow from below. This behavior can be seen in Fig. 2.6 which gives the conversion trajectories for the four particle size ranges used in our experiments at $600^\circ C$, 200 ml/min and 0.5% H_2S for the two directions of flow. Similar results were obtained at other temperatures, concentrations and flow rates. Since during flow from above, the particles are directly exposed to the flowing stream, mass transfer correlations for suspended particles are expected to be more reliable for this case. It was thus decided to use the experimental data for flow from above for the estimation of kinetic parameters and model testing.

2.4. Experimental Results

Sulfidation experiments were carried out under different reaction conditions to inves-

Figure 2.7 Conversion vs. normalized time results at 600°C and gas flow from below.

Figure 2.8 Conversion vs. normalized time results at 500°C and gas flow from below.

Figure 2.9 Temperature dependence of the reactivity of 53-62 μm particles for flow from above.

Figure 2.10 Temperature dependence of the reactivity of 297-350 μm particles for flow from above.

tigate the effects of reactive gas concentration, particle size and reaction temperature on the evolution of the reactivity of the solid. A preliminary discussion of general trends will be presented here. The experimental results will be discussed in more detail in the next section where their analysis using the generalized random pore model will be carried out.

A series of experiments was performed to determine the dependence of the reaction rate during ZnO sulfidation on the H_2S concentration. If the pseudosteady state assumption is made for the concentration profiles in the pore space and in the product layer – a reasonable assumption for the problem we study here – the conversion of the solid for a first order reaction should be uniquely defined by a time like variable (t') (Sotirchos and Zarkanitis, 1989)

$$t' = \int_0^t \frac{c_f}{c_f^*} dt \quad (2.2)$$

with c_f being the concentration in the bulk of the gas phase and c_f^* a reference concentration. Therefore, if the reaction trajectories (conversion vs. time curves) that were obtained in our experiments were replotted as conversion vs. normalized time, the latter defined from eq. (2.2) for constant concentration as (real time) $\times$ (percentage of H_2S in the inlet stream), they should bundle together for each pair of particle size and reaction temperature for a reaction of first order. This was found to be true, within the repeatability and reproducibility of our experiments, for all the sulfidation temperatures and particle sizes used in our study. The conversion vs. normalized time curves for sulfidation runs conducted at 600 and 500°C for two particle sizes (53-62 and 297-350 μm) and reactive gas flow upward are shown in Figs. 2.7 and 2.8, respectively. Similar conclusions about the order of the reaction were reached by Westmoreland et al. (1977), who observed a linear relationship between the initial reaction rate and the H_2S concentration. However, our results suggest that this is the case at all conversions and not only initially.

The experimental results for particles of different size, such as those presented in Fig. 2.6 showed that the reaction occurs under strong intraparticle diffusion limitations and that intraparticle diffusion must be considered in the analysis of the experimental data. As the reaction temperature rises, the intrinsic reactivity of the solid, the diffusivity in the pore space, and the diffusivity in the product layer increase; hence, one expects

higher reaction rates at higher temperature. Such a trend is clearly seen in Fig. 2.9 which presents results for 53-62 μm particles reacted with 0.5% H_2S , 200 ml/min flow rate, and reactive gas flow downward. However, the temperature effect is not as strong for large particles (297-350 μm) sulfided under the same conditions as the 53-62 μm particles of Fig. 2.9 (see Fig. 2.10). The experimental data at 300°C in Figs. 2.9 and 2.10 show significantly lower reaction rates than those at the other sulfidation temperatures. The reasons for this behavior will be discussed later.

The differences in the temperature effect for the two particle sizes are easily explained when one realizes that the reaction rate constant and the diffusivity in the product layer, which vary exponentially with the temperature, are controlling the observed reaction rate of 53-62 μm particles and that the intraparticle diffusion, which is affected rather weakly by the temperature, is the controlling step for the sulfidation of 297-350 μm particles. The weak effect of the reaction temperature on the sulfidation rates of porous sorbents of large sizes was also noticed in other studies. For instance, Focht et al. (1988) observed that the sensitivity of the overall reactivity of 3/16" extrusions of zinc ferrite during sulfidation in a thermogravimetric reactor was low in the temperature range of 500-700°C. Similar observations were made by Yumura and Furimsky (1985) for the sulfidation of cylindrical pellets (1.5mm in diameter and height) in a fixed-bed reactor.

2.5. Analysis of the Experimental Data and Discussion

The generalized pore model of Yu and Sotirchos (1987) was used to analyze the experimental data obtained in this study. This model considers a pore structure built around a three dimensional lattice with the bonds of the lattice functioning as axes of the pore segments of the network. The pore network is described by the pore size distribution of the pore segments and the coordination number of the lattice, z , the latter defined as the average number of pores emanating from a site. The length of the pore segments is assumed to be distributed independently of the pore size. For a given lattice structure the coordination number determines the accessibility of the network, that is, the functional relationship between the number of open pores and the number fraction of open pores that belong to inaccessible clusters of pores. There is a minimum number of open pores,

referred to as the percolation threshold of the structure, below which all open pores belong to inaccessible clusters, and consequently, diffusion and reaction cannot take place in the interior of the pore structure. For infinitely large coordination number, a thoroughly interconnected pore structure is obtained, and the equations of the generalized pore model reduce to those describing evolution in a pore structure consisting of randomly overlapping, infinitely long cylindrical capillaries (Sotirchos and Yu, 1985). Readers interested in the details of the generalized pore model are advised to consult the papers of Yu and Sotirchos (1987) and Zarkanitis et al. (1990).

Comparison of Experimental Results and Model Predictions

The reaction rate constants at different sulfidation temperatures were calculated from the initial rate of the reaction of 53-62 μm particles. Use of mass transfer correlations for flow past spherical particles (Bird et al., 1960) showed that the Sherwood number was about 2 (based on diameter) and practically independent of particle size. This value was thus used to determine the mass transfer coefficient. The initial reaction rates were corrected for the effects of intraparticle diffusion by using the analytical expression for the effectiveness factor of a first-order reaction (Smith, 1981). The reaction rate constant estimated through this procedure obviously depends on the structure of the solid through the dependence of the effectiveness factor on the effective diffusivity.

A Bethe network (Fisher and Essam, 1961), a tree-like structure, was used to obtain the accessibility function of the pore network. The diffusion coefficient in the product layer and the coordination number of the network were used as free parameters. They were determined under the constraints that the coordination number be the same at all reaction conditions and that the diffusion coefficient depends only on the reaction temperature. We found that a coordination number (z) equal to 8 provided the best fit between model predictions and experimental data at all conditions. Although only the results for flow from above were employed in our analysis, it should be pointed out that a smaller coordination number of 3.5 (or, equivalently, 5 for a regular lattice representation of the pore network) had to be used to get satisfactory agreement between model and experiment for flow in the reactor tube from below.

Table 2.1. Initial reaction rates (0.5% H_2S in N_2 , 53-62 μm particles, and reactive gas flow downward), effective diffusivities (estimated from the generalized pore model for $z = 8$ and $z = \infty$), effectiveness factors, and reaction rate constant (k_s) with and without correction for intraparticle diffusion.

Temperature ($^{\circ}C$)	300	400	500	600
Reaction Rate $\times 10^{10}$, ($gmol/cm^2/s$)	2.045	2.909	3.241	3.520
$D_e^{z=8} \times 10^2$, (cm^2/s)	0.725	0.799	0.886	0.928
Effectiveness factor, $\eta^{(z=8)}$	0.909	0.866	0.846	0.826
$k_s^{z=8} \times 10^3$, (cm/s)	2.116	3.708	4.863	6.111
$D_e^{z=\infty} \times 10^2$, (cm^2/s)	0.828	0.916	0.997	1.072
Effectiveness factor $\eta^{(z=\infty)}$	0.919	0.882	0.864	0.847
$k_s^{z=\infty} \times 10^3$, (cm/s)	2.093	3.644	4.761	5.962
$k_s \times 10^3$, (cm/s) (no correction, $\eta = 1$)	1.923	3.213	4.113	5.047

The initial reaction rates at 300, 400, 500, and 600 $^{\circ}C$ and the estimated reaction rate constants at these temperatures for $z = 8$ and $z = \infty$ are given in Table 2.1. Table 2.1 also shows the initial values of the effective diffusivity and the effectiveness factor for $z = 8$ and $z = \infty$. For finite z , the effective diffusivity was computed using the effective medium theory-smooth field approximation (EMT-SFA) approach of Burganos and Sotirchos (1987), according to which

$$D_e = \frac{\hat{\epsilon} \langle D(R)R^2 \rangle_e}{3 \langle R^2 \rangle_a} \quad (2.3)$$

R is the pore size, and $\hat{\epsilon}$ is the porosity that the pore structure would have if all pores of initial size R_0 had size R at time t . (Some pores of size R_0 may have become inaccessible during the reaction, and hence, their size will be different from R . Obviously, $\hat{\epsilon}$ is equal to the initial porosity at time zero.) $D(R)$ is the diffusion coefficient in a cylindrical capillary of radius R , computed using $D(R) = D_B D_K(R) / (D_K(R) + D_B)$, with D_B being the bulk diffusivity of H_2S in N_2 and $D_K(R)$ its Knudsen diffusivity in a pore of radius R . $\langle D(R)R^2 \rangle_e$ is the effective medium average of $D(R)R^2$ obtained from the equation

(Kirkpatrick, 1971)

$$\int_{R_0} \frac{\langle D(R)R^2 \rangle_e - D(R)R^2}{D(R)R^2 - (\frac{1}{p_c} - 1) \langle D(R)R^2 \rangle_e} l_0(R_0) dR_0 \quad (2.4)$$

$l_0(R_0)dR_0$ is the length per unit volume (or number per unit volume for uniform length) of pores with size in $[R_0, R_0 + dR_0]$, and p_c is the percolation threshold of the pore network (equal to $1/(z - 1)$ for a Bethe lattice and $2/z$ for a regular lattice). $\langle R^2 \rangle_a$ is the arithmetic average of R^2 with weight fraction $l_0(R_0)$. $l_0(R_0)$ is extracted from the pore size distribution of the solid (Yu and Sotirchos, 1987). For an infinitely large coordination number, $p_c = 0$ and $\langle D(R)R^2 \rangle_e = \langle D(R)R^2 \rangle_a$. Equation (2.3) then yields an effective diffusivity value that is almost identical to that obtained by just averaging the diffusivity of a pore of radius R over the pore size distribution for randomly oriented pores, i.e.,

$$D_e = \frac{1}{3} \int_R D(R) \epsilon(R) DR \quad (2.5)$$

with $\epsilon(R)dR$ being the porosity due to pores in the size range $[R, R + dR]$. (The diffusivity given by eqs. (2.3) and (2.4) for $z = \infty$ is identical to that obtained from eq. (2.5) only if the length distribution density function, $l_0(R_0)$, is determined from the initial porosity density function, $\epsilon_0(R_0)$, without correcting for the effects of pore overlapping, that is, by writing $l_0(R_0) = \epsilon_0(R_0)/(\pi R_0^2)$.) Since infinite coordination number implies perfectly interconnected pore network, the effective diffusivities for $z = \infty$ are larger than those for $z = 8$, by about 15% on the average (see Table 2.1). Correction of the measured reaction rates for intraparticle diffusion gives reaction rate constants larger by about 10-20%. Because of the larger effective diffusivity the correction is somewhat smaller in the case of infinite coordination number.

Fitting of the reaction rate constants for $z = 8$ to an Arrhenius-type equation gave an activation energy of 3.5 kcal/mol. Tamhankar et al. (1981) reported similarly low activation energies (3.3 kcal/mol) for the sulfidation of iron oxide and attributed this result to an adsorption-desorption reaction mechanism with hydrogen sulfide decomposition as the controlling step. A higher activation energy (6.6 kcal/mol) was determined from the reaction rates that we measured in the temperature range of 400-650°C for particles not directly exposed to the reactive gas stream, that is, with the reactive mixture flowing upward

Figure 2.11 Model predictions vs. the experimental data at 600°C with 0.5% H_2S ($z = 8$; $D_P = 10^{-8} \text{ cm}^2/\text{s}$).

Figure 2.12 Model predictions vs. the experimental data at 500°C with 0.5% H_2S ($z = 8$; $D_P = 5 \times 10^{-9} \text{ cm}^2/\text{s}$).

Figure 2.13 Model predictions vs. the experimental data at 400°C with 0.5% H_2S ($z = 8$; $D_P = 2 \times 10^{-9} \text{ cm}^2/\text{s}$).

Figure 2.14 Model predictions vs. the experimental data at 300°C with 0.5% H_2S ($z = 8$; $D_P = 5 \times 10^{-10} \text{ cm}^2/\text{s}$).

in the hangdown tube. This last value is very similar to that reported by Westmoreland et al. (1977) (7.2 kcal/mol), estimated from experimental data in the temperature range of 300-700°C without correction for intraparticle diffusion.

The predictions of the generalized pore model are compared in Fig. 2.11 with the conversion vs. time data of Fig. 2.6 for flow from above. The comparison of the experimental data and model predictions at 500 and 400°C is given in Figs. 2.12 and 2.13, respectively, for two particle sizes (53-62 and 297-350 μm). Only the product layer diffusion coefficient was varied from one figure to another in Figs. 2.11-2.13 in order to fit the model predictions to the experimental data. ($D_P=1 \times 10^{-8} \text{ cm}^2/\text{s}$ at 600°C; $D_P=5 \times 10^{-9} \text{ cm}^2/\text{s}$ at 500°C; $D_P=2 \times 10^{-9} \text{ cm}^2/\text{s}$ at 400°C). The agreement between model and experiment should be deemed as excellent considering the relatively broad ranges of particle size and temperature covered by our experiments. The reactivity evolution curves shown in Figs. 2.11-2.13 are for 0.5% H_2S in the reactive mixture, but similar agreement between model predictions and experimental results was obtained for other concentrations of H_2S — as it should be expected to be the case from the results of Figs. 2.7 and 2.8.

Fig. 2.14 compares the predictions of the mathematical model for $D_P=5 \times 10^{-10} \text{ cm}^2/\text{s}$ with reactivity evolution curves for 53-62 and 297-350 μm particles measured at 300°C with 0.5% H_2S in the reactive mixture. With the exception of the initial stages of the reaction, there is practically no agreement between model and experiment in Fig. 2.14. In the experimental results, the reaction rate appears to go through a sharp decline after about 5 min of exposure of the sorbent particles to the H_2S-N_2 mixture. On the other hand, the mathematical model predicts a much slower decrease of the reaction rate and, as a result, much higher conversions for large reaction times. Lower reaction rates and incomplete conversions were also reported by Gibson and Harrison (1980) for sulfidation in the temperature range of 300-500 °C and were attributed to strong diffusional limitations in the product layer. We tested this explanation by computing reactivity evolution curves for D_P values smaller than that used in Fig. 2.14. We found that regardless of what D_P value we employed, it was impossible to make the model predictions agree with the experimental data. The best that we could do was to make the theoretical and experimental conversions agree at some reaction time. Below this time, the model underpredicted the conversion,

Figure 2.15 Effect of heat treatment under nitrogen on sorbent reacted at 300°C (53-62 μ m, 0.5% H₂S, and flow from above).

while the opposite behavior was observed at larger times.

Visual examination of the partially reacted samples at 300°C showed that the color of the sorbent had changed from white, in the beginning of the experiment, to yellow. This was not the case for samples reacted at the other temperatures, with the exception of those at 400°C which also exhibited slightly yellow color. Yellow deposits were also found to occur at the low temperature section of the outlet tube of the reactor. These observations point to the conclusion that sulfur deposits are formed within the reacting particles, probably by chemisorption, during reaction at low temperatures, which either block the pores of the sorbent or prevent the gaseous reactant from reaching the reaction interface. Formation of sulfur in the reactor can take place by thermal decomposition of H_2S in the gas phase. Sulfur may also be involved as an intermediate in the $\text{ZnO-H}_2\text{S}$ reaction, especially if the reaction proceeds through an adsorption-desorption reaction mechanism — as it is most probably the case.

The above explanation was tested by performing the following experiment: A sample of $53\text{-}62\ \mu\text{m}$ particles was reacted for 30 min in the $\text{H}_2\text{S-N}_2$ mixture (0.5% H_2S). Inert gas (N_2) was then sent through the reactor to stop the reaction, and the temperature was raised to 600°C . Loss of weight was observed as the temperature increased. The sample was kept at 600°C until the signal of the microbalance was stabilized (for about 50 min). The furnace was then cooled down to 300°C , and the sample was again exposed to the reactive mixture. The variation of temperature and sample weight during the above experiment is shown in Fig. 2.15. The weight shown in this figure has been corrected for the effects of buoyancy and hydrodynamic drag, using results of blank experiments. In agreement with the results shown in Fig. 2.14, the rate of weight gain decreases fast during the initial stages of the reaction. More than 50% of the weight gained during the sulfidation step is lost during exposure in an inert atmosphere to higher temperatures. Since ZnS is practically stable under the conditions of the experiment, this loss indicates that deposition of some species takes place during reaction at 300°C , thus supporting the explanation proposed in the previous paragraph. The reaction starts to take place with initially high rate, comparable to that seen for the fresh material, when the treated sample is exposed to the reactive mixture. However, the reaction rate again drops quickly to very

Figure 2.16 Model predictions vs. the experimental data at 600°C with 0.5% H_2S ($z = \infty$; $D_p = 10^{-8} \text{ cm}^2/\text{s}$).

Figure 2.17 Model predictions vs. the experimental data at 600°C with 0.5% H_2S ($z = \infty$; $D_p = 10^{-9} \text{ cm}^2/\text{s}$).

low levels as sulfur deposition on the sorbent starts to occur. It should be pointed out that the sulfur deposition may also be responsible for having lower experimental conversions at 400°C than what the model predicts since heat-treatment of partially reacted particles at 400°C under an inert atmosphere also caused some weight loss, much smaller though than that seen for the 300°C samples.

Application of an Arrhenius-type expression to the diffusion coefficients in the product layer that were determined by matching model predictions and experimental data in Figs. 2.11-2.14 gave the following result:

$$D_P = 3.153 \times 10^{-6} e^{-9920/RT} \quad (2.6)$$

The diffusivities computed from eq. (2.6) are in good agreement with product layer diffusivities reported in studies for other gas-solid reactions with solid product. For instance, a survey by Marsh and Urichson (1985) found an average of about $10^{-8} \text{ cm}^2/\text{s}$ for the diffusion of SO_2 in CaSO_4 at 850°C . Similar diffusivity values were also extracted by applying the generalized pore model (Zarkanitis et al., 1990) to the sulfation of calcined limestones.

Effect of z , D_P , and D_e on the Model Predictions

Since the small sorbent particles reach complete conversion, one might argue that it may be possible to describe the sorbent behavior by the random pore model of Sotirchos and Yu (1985) which does not allow for inaccessible pore volume formation. This model considers a structure of infinitely long pores, and it is thus equivalent to the generalized pore model for infinite coordination number. Fig. 2.16 shows the comparison of the experimental data of Fig. 2.11 with the generalized pore model predictions for $z = \infty$ and the product layer diffusivity used for $z = 8$ ($D_P = 10^{-8} \text{ cm}^2/\text{s}$). We see that the model predicts higher reaction rates at all times and for all particle sizes. This behavior suggests that it may be possible to improve the results for $z = \infty$ by using a smaller D_P value. However, as the results of Fig. 2.17 show this does not turn out to be the case. The small particles react under insignificant intraparticle mass transport limitations, and therefore, their reaction trajectories are strongly influenced by the product layer diffusivity

Figure 2.18 Variation of the effective diffusivity with the conversion for different models at 600°C.

Figure 2.19 Model predictions vs. the experimental data at 600°C with 0.5% H_2S for variable tortuosity ($z = \infty$; $D_P = 10^{-9} \text{ cm}^2/\text{s}$).

over the whole conversion range. The reactivity of the large particles, on the other hand, is influenced by the product layer diffusivity only during the initial stages of the reaction. For large reaction times, the conversion vs. time results of large particles (especially those for the 297-350 μm particles) are not affected significantly by a change in the product layer diffusivity since in this case the most important parameter of the process is the effective diffusivity.

Fig. 2.18 presents the variation with the conversion of the effective diffusivity for $z = \infty$ (solid curve), given by eqs. (2.3) and (2.4) for $p_c = 0$ or approximately by eq. (2.5), and $z = 8$ (dashed curve), given by eqs. (2.3) and (2.4). Shown in the figure is also the ratio of the two diffusivities, $D_e^{z=\infty}/D_e^{z=8}$. Multiplication of this ratio by 3 gives the variable tortuosity factor that must be used, instead of 3, in eq. (2.5) to reproduce the $D_e^{z=8}$ diffusivity at all conversions. The results of Fig. 2.18 show that the effective diffusivity for infinite coordination number (see also Table 2.1) is larger than that for $z = 8$. The difference between the two diffusivities increases, almost exponentially, with the conversion. The faster decrease of the effective diffusivity for $z = 8$ is mainly due to the closure of the small pores and the concomitant decrease of the effective coordination number of the pore network.

The dotted effective diffusivity vs. conversion curve of Fig. 2.18 and the corresponding diffusivity vs. conversion ratio curve are given to show that the behavior predicted for finite coordination number may somehow be reproduced for $z = \infty$ if a tortuosity factor that increases exponentially with the conversion is employed. This shows that if we do not consider a network of finite coordination number, the predictions of the pore model can be made to agree with the experimental data only by using artificially low values of effective diffusivity that are inconsistent with the structure assumed in the construction of the pore model. Actually, this is more or less what is usually done in the literature when simple structural models are successfully used to reproduce experimental data for gas-solid reactions with solid product. The predictions of the mathematical model with $z = \infty$ but with $\tau = 3e^{0.5\xi}$ (see Fig. 2.18) are compared with the experimental data at 600°C in Fig. 2.19. It is seen that it is indeed possible to obtain good agreement for $z = \infty$, comparable to that obtained for finite z , by using variable tortuosity. This is a very important obser-

Figure 2.20 Effect of coordination number on the model predictions (600°C and $0.5\% \text{ H}_2\text{S}$).

Figure 2.21 Effect of diffusivity in the product layer on the model predictions for $z = \infty$ (600°C and $0.5\% \text{ H}_2\text{S}$).

vation since the mathematical model for $z = \infty$ (or equivalently, infinitely long pores) is much simpler (Sotirchos and Yu, 1985). However, one must resolve the problem of what expression to use for the variable tortuosity factor.

The results of Fig. 2.18 point to the conclusion that the coordination number of the pore network influences the predictions of the mathematical model mostly through its effects on the evolution of the effective diffusion coefficient. This is also suggested by the results of Fig. 2.20, which presents conversion vs. time curves for four ranges of particle size for $z = 8$ and $z = 4$. It is seen that the coordination number has practically no influence on the results for the small particles since in this case reaction occurs under insignificant mass transport limitations. It should be pointed out that the coordination number has in general much stronger effects on the intraparticle effective diffusivity and conversion vs. time results than those seen in Figs. 2.18 and 2.20. As Fig. 2.2 shows, however, the pore size distribution of the sorbent used in the present study is narrow, and consequently, changing the connectivity of the pores does not have a very strong effect on the resistance for intraparticle mass transport.

We saw in Fig. 2.17 that the product layer diffusivity affects the reaction trajectories of small particles over the whole conversion range, while those of the large particles tend to be affected only at the initial stages of the reaction. However, as Fig. 2.21 shows this is not generally true. Very small product layer diffusivities may make diffusion through the product layer the controlling step of the reaction, leading in turn to weak dependence of the reaction trajectories on particle size. Fig. 2.21 presents conversion vs. time results predicted by the mathematical model for $z = \infty$ and two values of product layer diffusivity, much smaller than the value used to approximate the experimental data. We see that in accordance with the above observations, the effects of particle size on the conversion trajectories diminish with decrease of D_p .

2.6. Summary and Conclusions

A thermogravimetric investigation of the reaction of a porous zinc oxide sorbent with H_2S in N_2 was carried out. The pore structure properties of the solid were determined using mercury porosimetry and gas adsorption. Experiments were carried out to investigate

the effects of concentration, temperature, and particle size on the reactivity evolution (conversion vs. time) curves. It was found that the $ZnO-H_2S$ reaction is approximately of first order over the temperature range (300-600 °C) covered in our experiments. The reactivity of the solid, both intrinsic and overall, was found to depend rather weakly on temperature, but very strong dependence on particle size was observed. Very low conversions were observed at temperatures around 300°C. Visual examination of partially reacted samples in terms of color, along with the results of some test experiments, led us to conclude that the low reaction rates were most probably caused by deposition of sulfur within the sorbent particles.

The generalized pore model of Yu and Sotirchos (1987) was used to analyze the experimental data. This model accounts for reaction, transport of the reactive gas (diffusion of H_2S in the pore space and in the product layer and mass transfer in the surrounding gas phase), and evolution of the structure of the sorbent during sulfidation. Very good agreement was found to exist between model and experiment at reaction conditions that did not involve sulfur deposition on the sorbent. The connectivity of the pore structure of the solid, quantified by the coordination number (number of pores per node) of the pore network that was used to represent the structure of the solid, and the diffusivity in the product layer were used as free parameters in the comparison of the model predictions with the experimental data. Our results showed that the intraparticle diffusivity and its evolution with the conversion are the parameters that have the most influence on the predictions of the mathematical model. If a perfectly interconnected pore network is used to represent the structure of the solid (infinitely long pores or infinite coordination number), the model predictions can be made to agree with the experimental data only by using a conversion-dependent tortuosity factor in the expression for the effective diffusivity.

2.7. Notation

c_f	concentration of H_2S in the reactor, mol/cm ³
$D(R)$	diffusivity of H_2S in a pore of radius R , cm ² /s
D_B	bulk diffusion coefficient of H_2S in N_2 , cm ² /s
$D_K(R)$	Knudsen diffusivity of H_2S in a pore of radius R , cm ² /s

D_e	effective diffusivity, cm^2/s
D_P	diffusivity in the product layer, cm^2/s
$l_0(R_0)dR_0$	pore length due to pores with size $[R_0, R_0 + dR_0]$
p_c	percolation threshold of a network ($=1/(z - 1)$ for a Bethe lattice)
R	pore radius, cm
R_0	initial pore radius, cm
z	coordination number

Greek Letters

$\epsilon(R)dR$	porosity due to pores with size $[R, R + dR]$
τ	tortuosity factor

3. EFFECTS OF PORE STRUCTURE ON THE PERFORMANCE OF COAL GAS DESULFURIZATION SORBENTS

3.1. Introduction

Hot coal gas desulfurization processes are based on the capacity of various metal/metal oxide solids to react with hydrogen sulfide and other sulfur containing compounds to form metal sulfides. Several supported (on ceramic support) or unsupported metal/metal oxide sorbents have been studied experimentally for hot gas desulfurization. The solids studied include iron oxide, zinc oxide, zinc ferrite, zinc titanate, copper/copper oxide, and cobalt titanate (e.g., see studies of Gibson and Harrison (1980), Tamhankar et al. (1981) and (1986), Lew et al. (1989), Sa et al. (1989), Woods et al. (1991), Gangwal et al. (1989), Sick and Shwerdtfeger (1987), Anderson et al. (1984), and Jalan (1983)). The evaluation of candidate sorbents for desulfurization applications is mainly based on their desulfurization capacity, resistance to attrition and sintering, and regenerability. Zinc oxide is one of the most frequently used desulfurization sorbents, because of the extremely low H_2S concentrations (of the order of a few ppm or less) found in the exit stream of beds loaded with zinc oxide sorbents or sorbents containing zinc oxide mixed with other metal oxides.

ZnO reacts with H_2S according to the equation:

The sorbents used in hot coal gas desulfurization are highly porous, and consequently reaction mainly occurs in their interior at the interface between solid reactant and solid product. The replacement of an oxygen atom by a sulfur atom in the above reaction produces a solid (ZnS) which occupies more space than the solid reactant (ZnO). As a result, the porosity of the solid diminishes with the progress of the reaction, the pores of the solid may become plugged by solid product, and formation of inaccessible pore space may take place. If sulfidation occurs under significant intraparticle diffusional limitations, complete pore closure may first occur at the external surface of the sorbent preventing further reaction in the interior. The reaction of calcined limestones with SO_2 is a typical example of gas-solid reactions with solid product formation, where incomplete conversion

of the solid reactant may take place due to the formation of inaccessible pore volume (Zarkanitis and Sotirchos, 1989). Nevertheless, although a large number of experimental work has been carried out on the investigation of the reactivity and desulfurization capacity of various metal oxide sorbents for the H_2S removal from coal gas streams, limited work has been done on the characterization of these sorbents in terms of their pore size distribution and resistance for intraparticle diffusion.

Surface areas and pore volumes of unreacted and fully sulfided metal oxide sorbents measured in previous desulfurization studies showed a decrease in both the surface area and the porosity after reaction with H_2S (Jalan, 1983; Tamhankar et al., 1986; Ranade and Harrison, 1981; Sa et al., 1989). The variation of the internal surface area of the metal oxides with the progress of the desulfurization reaction was measured by Ranade and Harrison (1981), Caillet and Harrison (1982), and Sa et al. (1989). Caillet and Harrison analyzed their data by using a population of nonporous, spherical grains to represent the solid matrix in the sorbent. The sulfidation reaction causes an increase in the radius of each grain, and thus, the pore surface area predicted by the grain model (for nonoverlapping (unconsolidated) grains) increases with the progress of the reaction, in contrast to the experimental evidence. For this reason, Caillet and Harrison assumed consolidation of grains to account for loss of surface area and sintering effects and employed an empirical equation proposed by Ranade and Harrison (1981) to relate the surface area with the overall conversion of the solid. Sa et al. (1989) measured the pore volume of zinc ferrite pellets reduced and sulfided in the temperature range $420-850^\circ C$ at different conversion levels of the solid reactant. They found that the evolution of the pore volume with the extent of the sulfidation reaction does not depend on the reaction temperature at sufficiently low temperatures ($420-600^\circ C$), but sintering of the solid during the reduction and the sulfidation reactions may cause a significant pore volume loss at higher temperatures ($> 750^\circ C$).

This study aims to examine the effect of the initial pore structure of zinc oxide sorbents on the evolution of their reactivity with the progress of sulfidation. The reaction of a commercially available zinc oxide sorbent (catalyst G-72D) with H_2S in a thermogravimetric analysis system (TGA) was investigated in detail in our laboratory (see Section 2).

The analysis of the obtained reactivity data using the generalized random pore model of Yu and Sotirchos (1987) showed that the initial effective diffusivity and its evolution with the progress of the reaction is the factor influencing the most the desulfurization capacity of the sorbent. Sulfidation and pore structure characterization experiments are carried out in this study using a ZnO sorbent with different initial pore structure than that of the sorbent used in the previous experiments. Conclusions on the effects of pore structure on the sulfidation process are reached by comparing the reactivities of the two sorbents in relatively broad ranges of particle size, reaction temperature, and H_2S concentration. As in Section 2, the generalized random pore model is used to analyze the sulfidation data and obtain quantitative information on the effects of the various parameters of the process.

3.2. Materials

The solids used in this section were two zinc oxide sorbents, supplied in the form of 3/16" extrusions by United Catalysts (catalysts G-72D and C7-2). The extrusions were crushed and then sieved to the following particle sizes: 53-62, 88-105, 210-250, and 297-350 μm . A weight loss was observed when the fresh materials were heat-treated in nitrogen for 30 min, which on the average was found to be about 6% of the initial weight for the G-72D sample and 5% for the C7-2 sample. Loss of humidity and binding material are the most probable causes for the occurrence of this weight change. Chemical analysis of the C7-2 sorbent, performed by X-Ray Assay Laboratories Ltd., revealed the existence of other oxides, such as MgO (0.11%), Al_2O_3 (6.92%), SiO_2 (15.03%), K_2O (0.25%), TiO_2 (0.6%), Fe_2O_3 (0.26%), Na_2O (0.06%), P_2O_5 (0.05%), and CaO (0.11), in addition to ZnO (76.61%). The compositional analysis of the G-72D sorbent was given in Section 2.2.

A mercury porosimeter and a volumetric adsorption unit were used to measure the physical properties of fresh, heat-treated, and sulfided sorbents. The relatively large samples needed for pore structure characterization were prepared in a fluidized-bed reactor under reaction conditions similar to those used for reactivity measurements in a thermogravimetric analysis system (TGA). Fully sulfided samples were also prepared in a fixed-bed reactor. The bed consisted of a quartz tube of 1.5 cm in diameter loaded with about 5 g of 710-850 or 297-350 μm particles. The sorbent was reacted with 1.05% H_2S in nitrogen

Figure 3.1 Pore size distributions of the unreacted zinc oxide sorbents.

at 600°C. The concentration of H_2S in the effluent stream of the reactor was measured periodically using a Varian 3300 gas chromatograph equipped with an FPD detector. The samples used in the fluidized-bed experiments were exposed to the reaction temperature (600°C) for a longer time period than those used in the TGA reactor. It was reported by Ranade and Harrison (1981) that at this temperature sintering effects are practically nonexistent. We measured the pore size distribution of samples of both sorbents after heat treatment under N_2 for 3 hr. Insignificant differences were found to exist between the pore size distributions of these sorbents and those of samples heat-treated only for 30 min. It was thus concluded that the pore structure of the samples prepared in the fluidized-bed reactor was not affected by sintering effects.

The density of the solid matrix (skeletal density) of each sorbent (heat-treated and completely sulfided solid) was estimated from N_2 pycnometry measurements using the adsorption unit. The densities measured by the above method are shown in Table 3.1, with each value obtained as the average of five independent density estimates. The skeletal densities of Table 3.1 are in very good agreement with those estimated from the compositions of the sorbents. Sample C7-2 has smaller density than sample G-72D (both the oxide and the sulfide) because it contains a large fraction of SiO_2 .

Table 3.1. Skeletal densities of the unreacted (heat-treated) and fully sulfided sorbents.

ZnO Sample	G-72D	C7-2
Density of unreacted material, g/cm^3	5.4	4.8
Density of fully sulfided material, g/cm^3	4.0	3.8

3.3. Pore Structure Characterization Results

Fig. 3.1 presents pore size distribution curves for fresh and heat-treated pellets obtained from the mercury intrusion results by assuming a pore structure of long cylindrical capillaries. Heat treatment led to higher porosities for both sorbents and shifted the pore size distribution of the G-72D sample toward larger pore sizes. Specifically, heat treatment increased the total porosity of the G-72D sorbent from 48 to 53% and that of

the C7-2 sample from 54 to 59%. Since the solids were heat-treated before each sulfidation experiment at 600°C under nitrogen, the analysis of sulfidation data was based on the physical properties of the heat-treated materials. Negligible differences were found to exist between the pore size distributions of Fig. 3.1 and those obtained from mercury intrusion results using sorbents in particle form (210-850 μm). Larson and Morrow (1981) examined the effect of sample thickness on the pore size distribution obtained from mercury intrusion data using percolation theory to analyze mercury intrusion and extrusion in porous media. They concluded that the effects of sample size should be negligible for sample thicknesses two orders of magnitude larger than the pore radius of the analyzed material. The ratio between the smallest particle size (210-250 μm) used in our pore structure characterization studies and the most probable radius (i.e., the radius that corresponds to the largest slope in the cumulative porosity vs. pore diameter curves of Fig. 3.1) in the mercury porosimetry results (e.g., 200 Å for sample C7-2) is about 10^4 , indicating that our results are in agreement with the conclusions of Larson and Morrow.

The nitrogen adsorption-desorption isotherms of the heat-treated sorbents (unreacted and fully sulfided) are shown in Figs. 3.2 and 3.3. The volume of nitrogen adsorbed or desorbed is given in these figures in standard conditions. The G-72D and C7-2 samples used for the isotherms of Figs. 3.2 and 3.3 were heat-treated at 600°C for 30 min under N_2 and sulfided in a fixed-bed for 210 and 80 min, respectively, using 1.05% H_2S in nitrogen. The shape of the nitrogen isotherms of Figs. 3.2 and 3.3 indicated that all materials exhibit type H3 isotherm according to the IUPAC classification (or IV isotherm according to the BDDT classification (Gregg and Sing, 1982)), which according to Gregg and Sing (1982) is associated with capillary condensation in mesopores (40-1,000 Å in diameter). Comparison of the nitrogen isotherms of the unreacted and sulfided samples shows that the sulfides adsorb smaller amounts of nitrogen at all partial pressures and exhibit somehow broader hysteresis loops than the unreacted sorbents. The pore volume decrease after sulfidation is the result of having a solid product occupying more space than the solid reactant. The nitrogen adsorption data of the unreacted solids in Figs. 3.2 and 3.3 are in agreement with the mercury porosimetry data of Fig. 3.1. Not only the total amount of nitrogen adsorbed by sample C7-2 is higher than that adsorbed by sorbent G-72D, but the

Figure 3.2 Nitrogen isotherm of the heat-treated sorbent G-72D and its sulfide.

Figure 3.3 Nitrogen isotherm of the heat-treated sorbent C7-2 and its sulfide.

start of the sharp decline in the desorption branch of the isotherm of C7-2 corresponds to a larger relative pressure (P/P_0) (or equivalently to a larger pore radius) than in the case of G-72D.

Table 3.2. Analysis of the nitrogen isotherm data of the sorbents and their sulfides.

	Surface Area	Surface Area	Micropore Volume
	BET	t-method	t-method
	m^2/g	m^2/g	cc/g
G-72D - Fresh	33.27	2.023	0.0012
G-72D - Heat-Treated	26.57	2.808	0.0015
G-72D - Fully sulfided	7.80	—	—
C7-2 - Fresh	36.39	3.367	0.0015
C7-2 - Heat-Treated	27.72	0.56	0.00032
C7-2 - Fully sulfided	13.78	0.608	0.00025

The sorption isotherm data obtained for fresh, heat-treated, and fully sulfided solids were used for the computation of the BET surface area and the physical properties of the micropores (pores with diameter less than 40 Å). The obtained results are shown in Table 3.2. The t-method (De Boer et al., 1965) was applied for the calculation of the surface area and pore volume of the micropores. It is seen from the results of Table 3.2 that these pores account only for a small fraction of the overall surface area of the unreacted samples, which practically vanishes after completion of the sulfidation reaction. Heat treatment leads to loss of surface area for both sorbents, and further reduction in the surface area is seen to occur after the sulfidation reaction (threefold and twofold reduction for samples G-72D and C7-2, respectively). Similar changes in the pore structure of desulfurization sorbents after completion of the sulfidation reaction have been reported in some other studies. For instance, Tamhankar et al. (1986), who measured the surface area of mixed metal oxides, fresh and sulfided, observed decrease in the surface area by a factor between 3 and 6, but

Figure 3.4 Cumulative pore volumes of heat-treated sorbents computed from the mercury porosimetry and the nitrogen adsorption and desorption data.

for total surface areas smaller than those listed in Table 3.2.

The mercury porosimetry and gas adsorption methods for pore structure characterization are based on different physical phenomena, and as result, each exhibits its own limitations. While both methods provide structural information about mesopores, mercury porosimetry is unreliable in the microporosity region, and the same holds for gas adsorption for macropores. Mercury porosimetry gives questionable results in the microporosity region because at very high pressures heat effects and mercury and sample compressibility interfere with pore volume measurements. On the other hand, the gas adsorption method presents problems for relative pressures close to unity (i.e., large pore sizes), where a small uncertainty about the temperature of the analyzed sample can lead to very large errors in the estimated pore radii (Gregg and Sing, 1982).

The nitrogen adsorption and desorption data of Figs. 3.2 and 3.3 can be transformed to pore volumes, and thus be compared with the mercury porosimetry data of Fig. 3.1. The cumulative pore volume distributions of the heat-treated sorbents that were obtained from the mercury penetration data and the adsorption and desorption branches of the nitrogen isotherms for pores larger than 40 Å in diameter are shown in Fig. 3.4. In order to make the results of the two methods comparable, all curves are expressed as cumulative pore volume vs. pore diameter starting from the lowest limit of the pore size range although in mercury porosimetry we measure the cumulative volume of pores starting from the upper limit of the pore size range (see Fig. 3.1). Pore size distributions were extracted from the sorption data using the method of Barrett et al. (1951). This method accounts for adsorption (or desorption) of the adsorbate on the pore walls in addition to condensation in (or evaporation from) the pores filled (or emptied). It is assumed that pores filled (or emptied) during an increment (or decrement) of relative pressure have average radius equal to the sum of the arithmetic mean of the radii corresponding to the upper and lower values of the relative pressure of each step and the thickness of the adsorbed layer for the partial pressure corresponding to the average radius of each step.

The desorption branch of the isotherm is most frequently used in the computation of the pore size distribution of the analyzed sample because desorption is believed to be closer to thermodynamic equilibrium. It is believed, however, (Everett, 1979) that

the adsorption branch of the isotherm should be preferred for the determination of the pore size distribution when pore network effects are present. Pore network effects are also present in mercury porosimetry. The pore size distributions obtained from mercury porosimetry and gas adsorption data refer to infinitely long capillaries or pores arranged in space in such a way that every pore is connected to at least one larger pore located closer to the external surface. However, in an actual pore structure a pore is emptied during desorption (or filled during mercury intrusion) at the pressure corresponding to its own radius only if it is connected to the external surface of the porous network through a path involving larger pores. Otherwise, the pore is emptied during desorption (or filled during mercury intrusion) at the pressure that corresponds to the radius of the smallest pore that must be emptied (or filled) to establish a continuous path of emptied (or filled) pores leading to external surface. (In the case of gas desorption, the above discussion assumes that nucleation effects are absent.) Such effects are not present during adsorption provided of course that the system is given enough time at each partial pressure to attain thermodynamic equilibrium. Since large cavities or clusters of large pores are interpreted during the analysis of mercury intrusion or gas desorption data as having radius equal to that of the smallest of the pores through which they are accessed from the exterior of the porous medium, differentiation of the cumulative pore volumes of Fig. 3.4 gives a narrow and steep pore size distribution when the mercury porosimetry and the nitrogen desorption curves are used, while a much broader pore size distribution shifted toward larger pore sizes is predicted from the nitrogen adsorption data.

It follows from the above discussion that mercury intrusion and gas adsorption are equivalent processes provided that nucleation effects are absent and that all pores of the porous medium are filled with adsorbate during the adsorption process. In other words, the porosity distribution obtained from gas adsorption should be identical to that extracted from mercury intrusion data under the above conditions. As the results of Fig. 3.4 show, this is almost the case for the gas desorption and mercury intrusion pore volume distribution curves of the G-72D solid. Therefore, pores with size greater than the upper limit of the pore size range covered by the gas adsorption measurement (about 1,500 Å in diameter) account only for a very small fraction of the total porosity in sorbent G-72D.

Nevertheless, it is probably because of the existence of these pores that there are differences between the desorption and the mercury intrusion porosity distribution. Whereas in the desorption experiments all pores of size greater than 1,500 Å are empty when desorption starts, only the pores from this range that form clusters reaching the external surface of the particle are filled with mercury in the mercury intrusion experiments.

The behavior of the C7-2 sample is completely different from that of G-72D. Not only the mercury intrusion and nitrogen desorption pore volume distributions are different, but also the total pore volume filled with adsorbate in the range covered by gas adsorption-desorption measurements (up to 1,500 Å) is smaller than the pore volume filled with mercury. This result suggests that a significant fraction of pore space in sorbent C7-2 belongs to pores with size (diameter) greater than 1,500 Å. These pores are obviously absent from the mercury porosimetry results since only a small fraction of them forms clusters reaching the external surface of the porous medium. If the adsorption pore volume distributions are accepted as the true pore volume distributions of the solids, then the results of Fig. 3.4 show that the two sorbents have identical distribution of specific pore volume up to the point (about 500 Å) where the cumulative pore volume of G-72D tends to level off. The additional pore volume of sample C7-2, therefore, is almost exclusively due to pores larger than those encountered in the G-72D sample.

Information on the connectivity of the pores in the structures of unreacted and sulfided sorbents can also be obtained from the pore volume vs. pore size curves extracted from mercury extrusion (withdrawal) data. Such results are shown in Figs. 3.5 and 3.6 for the unreacted (heat-treated) sorbents and Fig. 3.7 for the completely sulfided solids. It is seen that in all cases there is not only hysteresis in the withdrawal of mercury from the pore space but permanent mercury entrapment in the structure as well. In other words, mercury does not withdraw from all pores it invades during the intrusion step even when the pressure is reduced down to atmospheric level. The hysteresis phenomenon in the mercury intrusion-extrusion data is in agreement with the analogous behavior seen in the adsorption-desorption isotherms (Figs. 3.2 and 3.3), offering further evidence that the pore space of the solid should best be represented by a network-like structure. In a network of interconnected pores, each pore is invaded by mercury at a pressure corresponding to

Figure 3.5 Primary and secondary mercury intrusion-extrusion data for the heat-treated C7-2 sample.

Figure 3.6 Primary and secondary mercury intrusion-extrusion data for the heat-treated G-72D sample.

Figure 3.7 Mercury intrusion-extrusion data for fully sulfided G-72D and C7-2 sorbents.

a radius that is generally smaller than its own, namely, the radius of the smallest of the pores in the path leading to the exterior of the porous medium. On the hand, mercury is withdrawn from a pore at a pressure corresponding to a radius that is, in general, larger than its own, namely, the radius of the pore that must be emptied to bring the receding front of mercury in contact with the pore. Of course, mercury can be withdrawn from a pore provided that there is still a path of filled pores leading to the external surface of the porous medium. Otherwise, the mercury contained in the pores remain permanently in the pore structure.

The volume of mercury entrapped in the interior of the C7-2 sample is larger, both on an absolute and relative basis (relative to the total pore volume), than that entrapped in solid G-72D. This is an indication that there is better interaction of pores in the interior of the second solid. (In rough terms, better interaction (higher connectivity) may be understood as more paths leading to the exterior of the porous medium, on the average, from a given pore.) However, since the C7-2 sample has more pore volume per unit mass, more mercury withdraws from its space than from sample G-72D, 0.21 cc/g and 0.16 cc/g, respectively. Since there is more 'well-interconnected' pore volume (pore volume that mercury can invade and withdraw from) per unit mass of unreacted solid available to be filled with solid product in sample C7-2, its completely sulfided form exhibits better pore connectivity characteristics than that of sample G-72D, as it is evident from the results of Fig. 3.7. For both solids, the mercury volume trapped in the sulfided samples is larger than that in the original samples, both on absolute and relative basis. Specifically, 0.107 cc/g of mercury remain trapped in the pore space of the C7-2 sulfide and 0.083 cc/g in the heat-treated unreacted sample (both values are expressed per gram of unreacted solid). The corresponding values for the G-72D sample are 0.052 and 0.025 cc/g, respectively. The higher relative increase in the amount of the trapped mercury in the G-72D sample is a consequence of having less space of reversibly invaded pore volume available in this solid. The increase in the amount of trapped mercury in the pore space is not surprising. Pores that remain filled with mercury in the heat-treated sample will most probably do so in the sulfide. If the size of these pores is large relative to the other pores, then there will be little change in their size during the sulfidation process. Moreover, there will be

additional mercury trapped in the interior of the porous particles because of plugging of some of the feeder pores by solid product.

Figs. 3.5 and 3.6 also present cumulative pore volume vs. pore diameter curves obtained from secondary mercury extrusion experiments, that is, experiments where mercury penetration is carried out starting from an intermediate pressure following complete mercury intrusion and partial extrusion up to that pressure. Primary and secondary extrusion curves are much more difficult to interpret than intrusion results even when a specific physical model for the pore structure of the solid is adopted. By redefining the pore size distribution of a porous medium in terms of injection and withdrawal curvatures (or equivalently, radii), Larson and Morrow (1981) were able to interpret primary and secondary extrusion curves of the type shown in Figs. 3.5-3.7 using percolation theory concepts. However, this does not solve the problem since one still needs the true pore size distribution in order to develop a model for reaction occurring at the gas-solid interface or reacted-unreacted solid interface. For the special case in which the pore structure consists entirely of ink-bottle (dead-end, noninteracting) pores, secondary extrusion curves can be analyzed using the Reverberi method (Reverberi et al., 1966; Svata, 1971; Gregg and Sing, 1982). For the two partial intrusion curves shown in Fig. 3.5, this method predicts that $(V'_B - V_B) - (V'_A - V_A)$ is the volume of the ink-bottle pores of size between D_1 and D_2 fed through necks of size between D_3 and D_1 . For the specific set of D_i 's of Fig. 3.5, it turns out that 0.068 cc/g is due to pores with size 2,000-3,000 Å fed through necks of diameter 320-2,000 Å. Similar results may be obtained for other D_3 values and other pairs of secondary extrusion curves. However, a structure of ink-bottle pores exhibits no permanent mercury entrapment, and therefore, it is inappropriate for the interpretation of the mercury extrusion data for the two sorbents of this study.

3.4. Reactivity Results

Reactivity experiments were carried out using the sorbents in particle form in order to better elucidate the effects of the intraparticle diffusional limitations on the sulfidation reaction. Experiments were carried out using all four ranges of particles that were isolated from the crushed extrusions: 53-62, 88-105, 210-250, 297-350 μm . The reactive gas

was 10,500 ppm H_2S in nitrogen, which was further diluted with nitrogen to the desired concentration. All experiments were performed under isothermal conditions in the range 400-600°C. Sulfidation experiments were conducted in the thermogravimetric analysis system (TGA) described in Section 2. The solid samples were placed on a 5 mm quartz pan suspended from the sample arm of the balance with platinum wire. The reactive mixture flowed downward in the reactor so that the particles were directly exposed to the entering reactive mixture.

Combination of large amounts of solid reactant and small reactive gas flow rates can lead to significant interparticle diffusional limitations, and to significant decrease of the reactive gas concentration at the exit stream (i.e., nondifferential operation of the TGA reactor). Test experiments were carried out to investigate the effects of sample weight and flow rate on the experimental data. On the basis of these experiments, it was concluded that use of less than 3 mg of sorbent and of flow rates of 200 ml/min or more would maintain almost differential operation of the TGA reactor at all times for the reaction rates observed in this study.

The reactivity evolution curves of the two zinc oxide sorbents are presented in the same figures to show the effect of the initial pore structure on the sulfidation rates in the TGA reactor. Such results are shown, as conversion vs. time curves, in Figs. 3.8, 3.9, and 3.10 for sulfidation at 400, 500, and 600°C, respectively. The same reaction conditions were used in the experiments for both sorbents with 0.5% H_2S in nitrogen as the reactive mixture. The effects of intraparticle diffusional limitations on the conversion vs. time trajectories intensified with increasing particle size at all temperatures. The particle size effects were much stronger for the G-72D sorbent. This behavior is most probably caused by the smaller porosity and pores of this sorbent and, hence, its larger resistance for intraparticle mass transport. The temperature effect on the conversion vs. time curves diminished with increasing particle size. Large particles are weakly influenced by the temperature since their overall reactivity is controlled by the effective diffusivity of H_2S in the pore space, which changes slowly with the temperature (proportionally to the square root of the temperature for diffusion in the Knudsen regime). On the other hand, the behavior of small particles is controlled by the local reactivity of the solid (intrinsic

Figure 3.8 Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for different particle sizes sulfided at 400°C with 0.5% H_2S .

Figure 3.9 Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for particles of 53-62 and 297-350 μm , sulfided at 500°C with 0.5% H_2S .

Figure 3.10 Comparison between the experimental conversion vs. time curves of sorbents C7-2 and G-72D, for particles of 53-62 and 297-350 μm , sulfided at 600°C with 0.5% H_2S .

Figure 3.11 Experimental data for 53-62 μm particles of sorbent C7-2 reacted with various H_2S - N_2 mixtures at 600°C.

Figure 3.12 Experimental data for 297-350 μm particles of sorbent C7-2 reacted with various $\text{H}_2\text{S}-\text{N}_2$ mixtures at 600°C.

Figure 3.13 Conversion vs. normalized time curves for sulfidation of sorbent C7-2 at 600°C.

reactivity and diffusion in the product layer), which show much greater sensitivity to the reaction temperature. The reaction trajectories at 400°C (Fig. 3.8) display lower reaction rates at high conversions than what one would expect on the basis of the results at higher temperatures (especially for $53\text{-}62\ \mu\text{m}$ particles). The reasons for this behavior were discussed in Section 2 and will be outlined later during the analysis of the reactivity results.

C7-2 particles of $53\text{-}62\ \mu\text{m}$ and $297\text{-}350\ \mu\text{m}$ were exposed to different H_2S concentrations at 600°C (Figs. 3.11 and 3.12). Higher reaction rates were measured for both particle sizes when the H_2S concentration in the reactive mixture increased. The initial reaction rates of particles of $53\text{-}62\ \mu\text{m}$ and $297\text{-}350\ \mu\text{m}$ were proportional to the H_2S concentrations at all sulfidation temperatures, implying that the reaction is of first-order with respect to H_2S . For a first-order reaction, the conversion vs. normalized time (defined as the product of the real reaction time and H_2S percentage in the reactive gas) curves should be independent of the reactive gas concentration, provided that the pseudosteady state approximation in the intraparticle space is valid — a reasonable assumption for the sulfidation reaction. The results of Fig. 3.13 show that this indeed is the case for the C7-2 solid.

3.5. Analysis of the Experimental Data

The generalized random pore model of Yu and Sotirchos (1987) was used to analyze the experimental reactivity data for the two sorbents. This model considers that the pore space in each porous material can be represented using pore segments whose axes are arranged as a three-dimensional lattice. A Bethe lattice (a tree-like structure) was used in the application of the generalized random pore model to our results. The only parameter needed to describe the topology of such a lattice is its coordination number, z , that is, the number of bonds (pores) emanating from a node.

The effective stoichiometric volume ratio (volume of reacted solid phase per unit volume of unreacted solid phase), Z , and the effective molar volume (volume of unreacted solid phase per mole of solid reactant), v_s , of each sorbent are needed in the application

of the generalized random pore model. They are obtained from the equations:

$$Z = \psi_{ZnO} \times \frac{v_{ZnS}}{v_{ZnO}} + (1 - \psi_{ZnO}) \quad (3.1)$$

$$v_s = \frac{v_{ZnO}}{\psi_{ZnO}} \quad (3.2)$$

with v_i being the molar volume of the solid i and ψ_{ZnO} the volume fraction of ZnO in the unreacted solid phase. Obviously, for a sorbent containing only ZnO , $Z = v_{ZnS}/v_{ZnO}$ and $v_s = v_{ZnO}$. The Z and v_s values for the two sorbents are shown in Table 3.3. Because of its relatively high SiO_2 content, the effective stoichiometric volume ratio of sorbent C7-2 is smaller and its effective molar volume larger than the respective quantities for sorbent G-72D.

Table 3.3. Data for the application of the generalized random pore model.

ZnO Sample	G-72D	C7-2
Z	1.54	1.38
v_s	17	24

Use of mass transfer correlations for flow past spherical particles (see eq. 3.48) showed that the Sherwood number at the experimental conditions used in our experiments was about two (based on the diameter) and practically independent of particle size. This value was thus used to determine the mass transfer coefficient. The reaction rate constant was estimated from the initial rate data using the analytical expression for the effectiveness factor of a first-order reaction in spherical particles (eq. 3.45). Obviously, the estimated reaction rate constant depends on the structural model for the porous sorbent through its dependence on the effective diffusivity.

We chose to use the pore size distribution determined from the mercury intrusion data of the heat-treated sorbents in the application of the model because mercury intrusion is, in general, the only method that can provide information on the whole pore volume of a porous medium, with the exception of solids possessing a significant fraction of micropore volume. As it was mentioned during the discussion of the pore structure

characterization data, mercury extrusion does not give information on the void space of the porous medium where mercury is trapped, and adsorption-desorption isotherms do not provide reliable data for large pore sizes, that is, pores with capillary condensation pressure very close to the atmospheric. Because of the presence of hysteresis in the nitrogen adsorption-desorption data and mercury penetration-retraction results, the apparent pore size distributions derived from the mercury intrusion data (Fig. 3.1) should be corrected for pore network effects. We decided not to do this since, in order to correct the pore size distribution, it would be necessary to make additional assumptions about the length of the pore segments and its relation to the particle size (Larson and Morrow, 1981; Mishra and Sharma, 1988). Besides, the simulation results of Zarkanitis (1990) showed that results quantitatively and qualitatively similar to those obtained using the apparent pore size distribution may be obtained by using the true pore size distribution with a smaller coordination number.

In Section 2, we applied the generalized random pore model to the sulfidation of sorbent G-72D and found very good agreement between theory and experiment in the temperature range 400-600°C when the coordination number (z) was set equal to 8. The analysis of the experimental results for sorbent C7-2 followed the same procedure as in Section 2. The product layer diffusivity and kinetic constant values that were determined by fitting the model predictions to the experimental data for sorbent C7-2 are shown in Table 3.4, along with the kinetic constants for sorbent G-72D. Our preliminary analysis of the experimental data for sorbent C7-2 showed that D_P values similar to those used for sorbent G-72D had to be employed to obtain good agreement between model and experiment. In view of this finding, the product layer diffusivity was set equal at each temperature to the value for solid G-72D, and the coordination number was used as the only adjustable parameter. It is seen from the results of Table 3.4 that the intrinsic constants are not much different from each other at the same temperature. For Arrhenius-type dependence on temperature, the resulting value of activation energy is 3.4 kcal/mol for sorbent C7-2 and 3.5 kcal/mol for sorbent G-72D. (The activation energy for sorbent G-72D also includes the reaction rate measured at 300°C.) The corresponding activation energy for the dependence of D_P on temperature is 9.9 kcal/mol.

Figure 3.14 Comparison of the generalized random pore model predictions with the experimental data at 600°C for samples C7-2 and G-72D.

Figure 3.15 Comparison of the generalized random pore model predictions with the experimental data at 500°C for sample C7-2.

Figure 3.16 Comparison of the generalized random pore model predictions with the experimental data at 400°C for sample C7-2.

Table 3.4. Diffusion coefficients in the product layer and reaction rate constants used in the application of the generalized random pore model.

Temperature ($^{\circ}C$)	600	500	400
k_s (cm/s) for C7-2	5.97×10^{-3}	4.30×10^{-3}	3.30×10^{-3}
k_s (cm/s) for G-72D	6.11×10^{-3}	4.86×10^{-3}	3.71×10^{-3}
D_P (cm ² /s) for both solids	1×10^{-8}	5×10^{-9}	2×10^{-9}

The predictions of the mathematical model are shown in Figs. 3.14, 3.15, and 3.16 for the three temperatures used in our study (600, 500, and 400 $^{\circ}C$, respectively). Fig. 3.14 also presents the experimental and theoretical curves for 297-350 μm particles of the G-72D sorbent reacted at 600 $^{\circ}C$. The results of Figs. 3.14 and 3.15 show that the generalized random pore model produced very good approximations for the experimental reactivity evolution curves of sorbent C7-2 at 600 and 500 $^{\circ}C$ for infinite coordination number ($z = \infty$). Good agreement between theory and experiment was obtained for all four particle sizes even though the coordination number – which had to be the same for all cases – was the only parameter used to fit the model predictions to the experimental data. For the conversion vs. time results obtained at 400 $^{\circ}C$ (Fig. 3.16), however, it was impossible to make the model predictions agree with the experimental data at high conversions no matter what values of D_P and z were used. While there is a drastic reduction in the overall reaction rate in the experimental data after about 10 min exposure to the reactive mixture with insignificant sulfur uptake occurring beyond this point, the model predicts complete conversion for both particle sizes. The model can be forced to predict incomplete conversion within the time interval of the experimental data of Fig. 3.16 by using much smaller D_P values, but at the expense of underestimating significantly the reaction rate and conversion during the initial stages of the process.

Similar behavior was also encountered with the G-72D sorbent at 300 $^{\circ}C$ and to a lesser extent at 400 $^{\circ}C$ in Section 2, where we postulated that it is caused by sulfur deposition, most probably by chemisorption, within the reacting particles. This conclusion was based on a number of observations. For instance, it was observed that partially

reacted sorbents at 400°C or below had yellow color that became darker with decreasing sulfidation temperature. After heat treatment at 600°C under N_2 , these samples lost weight and obtained the same whitish color as samples sulfided at 600°C . Moreover, the heat-treated, partially reacted samples reacted with rate similar to that of the fresh sorbent when reexposed to the reactive mixture at the reaction temperature. Sulfur deposition interferes with the progress of the sulfidation reaction since it either blocks the pores or prevents the reactant from reaching the reaction interface. At the early stages of the process, however – that is, before the pores are blocked or the pore surface is covered by sulfur – sulfur deposition may lead to an apparent enhancement of the overall reactivity of the sorbent.

Infinite coordination number is indicative of a perfectly interconnected pore structure, which may be viewed as one consisting of infinitely long cylindrical capillaries. A structure of infinitely long pores for sorbent C7-2 is in apparent contradiction with the pore structure characterization data, which showed that both sorbents exhibit hysteresis in the mercury intrusion-extrusion and gas adsorption-desorption curves. Moreover, having a higher coordination number (higher connectivity) of pores in sorbent C7-2 than in sorbent G-72D conflicts with our findings that more mercury, on a relative basis, remained permanently entrapped in the structure of the former sorbent during extrusion. However, the various conclusions that we reached from the analysis of the pore structure characterization data about the extent of interaction of pores of different size in the porous sorbents refer to the true pore size distribution of the solids. On the other hand, the coordination number used to reproduce the experimental data was determined on the basis of the pore size distribution extracted from the mercury intrusion data, which – as it was explained during the discussion of the pore structure data – is shifted toward smaller pore sizes relative to the true pore size distribution of the solid.

We pointed out in the previous section that if pore volume data from the nitrogen adsorption data are assumed to be representative of the true pore size distribution – as it is most probably the case – the results of Fig. 3.4 indicate that the additional pore volume of sample C7-2, relative to that of G-72D, is mainly due to pores larger than those found in the second sample. Nevertheless, the mercury-intrusion pore size distributions

of the two solids are narrow and similar to each other. This indicates that the mercury intrusion data are influenced more by network and pore connectivity effects in the case of sorbent C7-2. It is probably because of this reason that the coordination number that must be used in the mathematical model to reproduce the experimental data is larger for sorbent C7-2 despite the lower connectivity of its pore space that is evidenced by the gas adsorption-desorption and mercury intrusion-extrusion data. It must be pointed out that depending on the topological features of the pore space of a solid, it is possible the pore size distribution obtained from mercury intrusion to overcompensate for network and finite connectivity effects in the pore space. In such a case, it may be necessary to consider that the pores in the solid are 'better' interconnected than those in a structure of infinitely long pores (that is, use tortuosity factors smaller than 3) in order to reproduce experimental reactivity data using a pore-based mathematical model.

The porosity data of Fig. 3.1 for the heat-treated sorbents indicate presence of some porosity belonging to pores with diameter less than 100 Å. The existence of a significant fraction of pore volume for pores of such size is not corroborated by the pore volume data extracted from the nitrogen isotherm, implying that the mercury porosimetry data overestimate the volume of pores of diameter less than 100 Å (most probably because of mercury and sample compressibility effects). For this reason, only pores of diameter larger than 100 Å were used in the analysis of the experimental data. The most probable pore diameter of both solids is larger than 200 Å, and therefore, pores smaller than 100 Å are probably dead-end pores originating from the surface of larger pores or due to the roughness of the latter. Such pores participate in the sulfidation process during the early stages of the reaction only since they do not contribute to mass transport in the intraparticle space and are plugged with solid product at low conversion levels. Since infinite coordination number is used to reproduce the experimental data for sorbent C7-2, inclusion of pores of smaller radius has practically no effect on the model predictions since small through pores in a structure of perfectly interconnected or infinitely long pores contribute negligibly to mass transport in the intraparticle space. However, a larger coordination number has to be used (larger than 8) to satisfactorily approximate the experimental data for the G-72D sorbent when pores below 100 Å are included in the pore size distribution. In a typical

pore size distribution, small pores account for a small fraction of the total porosity but for a disproportionately large fraction of the total number of pores, and as a result, they play a very important role in a network of finite connectivity – as it is the case for solid G-72D. Notice that since the small pores contribute much more to the total surface area than to the pore volume, intrinsic reaction rate constants smaller than the values listed in Table 3.4 (by about 20% on the average) are obtained for both solids when the small pores are included in the pore size distribution.

Fig. 3.17 presents the evolution of the effective diffusivities of the two sorbents that are predicted by the mathematical model at 600°C . It is seen that the effective diffusivity varies in the same order as the overall reactivity of the two sorbents, with sorbent C7-2 having about two times larger initial effective diffusivity (viz. 1.73×10^{-2} vs. $9.03 \times 10^{-3} \text{ cm}^2/\text{s}$). Since the porosity diminishes with the progress of the reaction, the effective diffusivity predicted by the mathematical model decreases. The larger diffusivity of sorbent C7-2 is apparently due to its larger pore volume (per unit mass) and bigger pores. The investigation of the sensitivity of the generalized random pore model to its parameters for the sulfidation of sorbent G-72D that was carried out in Section 2 showed that the resistance for intraparticle mass transport is the factor that influences the most the predictions of the model.

The evolution of the pore size distribution of sorbent C7-2 with the progress of the reaction was studied by analyzing the pore structure of partially reacted samples by mercury porosimetry and gas adsorption. In order to obtain uniformly reacted samples, 710-850 μm particles were sulfided at 600°C with 1.05% H_2S in N_2 in a fluidized-bed reactor. The experimental mercury intrusion pore size distribution curves are compared with the model predictions in Fig. 3.18. Since the conversion varies along the radius of the particles, the theoretical pore size distributions were obtained by averaging the local pore size distribution over the intraparticle space. The experimental results follow the same qualitative trend as the model predictions, but there are significant quantitative differences between the two sets of data. While the theoretical pore size distributions move toward smaller pore sizes – as it is expected for a gas-solid reaction involving solid product that occupies more space than the solid reactant it replaces – the evolution of

Figure 3.17 Evolution of the effective diffusivity of sorbents C7-2 and G-72D at 600°C with the progress of sulfidation.

the experimental curves suggests that the most probable pore size of the distribution does not vary significantly with the progress of the reaction. This situation is much worse for the pore size distribution of the fully sulfided sample prepared in the fixed-bed reactor, also shown in Fig. 3.18, which appears to be shifted toward larger pores. It is believed that this behavior is caused by the exposure of the reacting particles to the water vapor produced by the sulfidation reaction. Particles sulfided in a fixed-bed reactor remain exposed to the product stream – which is practically a mixture of H_2O and N_2 – until the reaction front reaches them. On the other hand, particles reacted in a fluidized-bed reactor see high concentrations of H_2O only during the initial stages of the reaction when high reaction rates prevail. We tested this explanation by analyzing the pore size distribution of particles exposed to a mixture of 1% H_2O in N_2 at $600^\circ C$ for a period of 2 hr. The pore size distribution of the solid after exposure to water vapor was found to be shifted toward larger pores, though not as markedly as that of the sorbent that was fully sulfided in the fixed-bed reactor. More dramatic was the effect of water vapor on the extrusion branch of mercury porosimetry, with the hysteresis loop being much broader than that of the unexposed sorbent.

Fig. 3.19 compares the theoretical conversion profiles at 50% average conversion in 297-350 μm particles of the two sorbents sulfided at $600^\circ C$ with 0.5% H_2S in N_2 . In accordance with the reactivity results of Fig. 3.10 and the effective diffusivity evolution curves of Fig. 3.17, larger conversion gradients are present in the interior of the G-72D sorbent. In order to test the conversion profile predictions of the model, we used SEM/EDS (Scanning Electron Microscopy/Energy Dispersive Spectrometry) to obtain the sulfur and zinc maps over the cross-section of partially-reacted in the TGA, up to 50% conversion, particles of the two sorbents. The obtained results are shown in Fig. 3.20. The specimens were prepared by mounting the particles in epoxy resin and grinding the mounted sample to a depth of 150 μm . The results of Fig. 3.20 are in agreement with the theoretical conversion curves of Fig. 3.19 since they show that the average thickness of the region (shell) in which there is measurable concentration of sulfur in the sorbents is larger in the case of sorbent C7-2. Several cross-sections like those depicted in Fig. 3.20 were analyzed. In all cases, the thickness of the 'reacted' layer was relatively uniform along the periphery

Figure 3.18 Comparison of the pore size distributions obtained from the mercury porosimetry data of sample C7-2 sulfided at various conversions with the predicted by the mathematical model pore size distributions at the same conversions.

Figure 3.19 The mathematical model predictions for the conversion profiles in 297-350 μm particles at 50% average conversion for sorbents C7-2 and G-72D.

Sulfur and Zinc Maps for two Zinc Oxide Sorbents (297-350 microns) at 50% Conversion

Figure 3.20 Sulfur and zinc maps obtained from the SEM/EDS analysis of 297-350 μm particles of sorbents C7-2 and G-72D at 50% average conversion.

of the particles for the G-72D sorbent. The reaction front of the C7-2 solid, on the other hand, was highly irregular presenting several protrusions. A comparison of the sulfur maps of sorbent C7-2 with the corresponding SEM pictures of the same sorbent showed that in most cases, these protrusions surrounded large pores (cracks) of a few μm in size. It is probably these cracks that are responsible for the lower mass transport resistance and higher reactivity of the C7-2 sorbent. The presence of such large pores (cracks) is consistent with our observation that whereas the mercury porosimetry data for sorbent G-72D were practically independent of the particle size from the pellet size down to 53 μm , this was true for the C7-2 solid only for particles larger than about 200 μm . C7-2 particles of 53-62 μm size had much broader distribution of pore size and slightly smaller mercury retention volumes, indicating particle size effects on the accessibility of large pores in small particles.

3.6. Summary

A detailed investigation of the effects of pore structure on the performance of metal oxides used as sorbents for H_2S removal from hot coal gas was carried out by studying the evolution of reactivity and pore structure properties of two ZnO sorbents of differing pore structure. The structure of the sorbents, fresh and sulfided, was analyzed by mercury porosimetry and gas adsorption (N_2 at 77 K). Sulfidation experiments were carried out in a thermogravimetric analysis system using different size particles at various temperatures and concentrations. The distribution of sulfur in partially reacted particles of the two sorbents was measured using SEM/EDS. The samples used for pore structure characterization were prepared in fixed- and fluidized-bed reactor.

Our results showed very strong effects of pore structure on the overall reactivity of the two solids. Analysis of the reactivity and structure evolution data using a mathematical model showed that the pore structure influenced the performance of the sorbents mainly through its effects on the resistance for intraparticle mass transport. This finding was in accordance with the SEM/EDS sulfur distribution maps which showed that the sorbent with the higher reactivity had smaller conversion gradients, that is, the adsorbed sulfur was distributed over a larger area of the intraparticle space. The pore size distributions of the

two sorbents that were obtained from mercury intrusion-extrusion and nitrogen adsorption-desorption data, in conjunction with the reactivity evolution data and the mathematical model results, led to the conclusion that the performance of a desulfurization sorbent is controlled not only by its pore size distribution but its pore space connectivity as well, that is, the extent of interaction of pores of different size in its interior.

4. EXPERIMENTAL AND THEORETICAL INVESTIGATION OF THE REGENERATION OF SULFIDED SORBENTS

4.1. Introduction

The hot coal gas stream leaving a coal gasifier unit contains H_2S , among other sulfur-containing compound, which must be removed before use of this stream in a power production plant (e.g., integrated gasification combined cycle or gasifier-molten carbonate fuel cell system). The reaction of metal oxides with H_2S at high temperatures can be used for the cleanup of hot coal gas streams. The sorbent used for desulfurization must be regenerable, because use of the same solid for multiple sulfidation-regeneration cycles improves the efficiency of the electric power plant and minimizes the production of solid waste.

Zinc oxide is a regenerable material that can reduce the H_2S concentration of a coal gas stream to the level of a few ppm or less. During H_2S removal, the ZnO contained in the sorbent is converted to sulfide (ZnS), while during regeneration, air or another oxygen-containing gas mixture is used to oxidize the sulfide back to ZnO . When oxygen is used as the oxidizing agent, the regeneration reaction is the same as that encountered in the roasting of zinc sulfide ores. Several zinc oxide and ZnO -containing sorbents (e.g., $ZnO-CuO$, zinc ferrite, $ZnFe_2O_4-CuO$, and zinc titanate) have been investigated as candidate sorbents for the removal of H_2S from coal gas streams. Experimental studies where fresh sorbents consisting of ZnO or mixtures of ZnO with other metal oxides were reacted with H_2S -containing gas mixtures in TGA reactors are among others those of Gibson and Harrison (1980), Focht et al. (1986), Lew et al. (1989), Woods et al. (1991), and Gangwal et al. (1989). Regenerated zinc ferrite and zinc titanate sorbents were sulfided by Focht et al. (1986) and Gangwal et al. (1989). It was found that the desulfurization performance of the regenerated solids was similar to that of the unreacted sorbents. By treating the effective diffusivity in the pore space as a parameter, Focht et al. (1986) managed to reproduce the behavior of pellets going through multiple sulfidation-regeneration cycles using the unreacted (shrinking) core model.

Reagent grade zinc sulfide has been reacted with O_2-N_2 mixtures in a number of

past experimental studies. A relatively broad range is covered by the activation energies reported in the literature for the $ZnS-O_2$ reaction. For example: 50 *kcal/mol* by Cannon and Denbigh (1957); 38.1 *kcal/mol* by Rao and Kumar (1982); 84.3 *kcal/mol* by Prabhu et al. (1984); and 55 *kcal/mol* by Kimura (1989). Using nonporous ZnS , Cannon and Denbigh (1957) found that an Arrhenius-type expression for the dependence of the reaction rate constant on the temperature could fit the experimental data in the range 680-830 °C. Significant deviations from an Arrhenius-type behavior were observed at higher temperatures, and this was attributed to the effects of diffusional limitations in the oxide layer on the observed reaction rates. Prabhu et al. (1984) formed porous pellets by compacting zinc sulfide powder. The slope of the Arrhenius-type plot that they constructed from the initial oxidation rates in the temperature range of 480-600°C changed above some temperature that decreased with decreasing initial porosity of the sample. The last observation led to the conclusion that transition from chemical reaction control on the observed rates to partial diffusion control took place.

The regeneration of metal oxide sorbents is a gas-solid reaction that involves pore structure changes. The sulfidation of a porous sorbent leads to a less porous solid, while the opposite occurs during regeneration. If we consider that the sorbent is fully sulfided and regenerated and that the overall initial volume of the solid reactant is preserved, then the regenerated solid should possess the same porosity as the unreacted sorbent. However, this does not necessarily mean that the physical properties (surface area and pore size distribution) and the desulfurization capacity of fresh and regenerated sorbents are the same. For instance, the reaction of ZnS with O_2 was examined using reagent grade nonporous solids by Kimura (1989). SEM micrographs showed roughness and porosity in the place of the initially smooth, nonporous grains. Rao and Kumar (1982) determined experimentally the conversion profiles of partially oxidized pellets. They found that at the reaction conditions of their study – pellets of 1.2 *cm* in diameter and 3 *cm* in height of 30-50% initial porosity were reacted with air in the range 600-820 °C – a reaction front and not a sharp interface existed in the porous pellets. Their experimental data were in agreement with the predictions of a mathematical model that represented the solid matrix by a population of dense spherical grains.

The regeneration kinetics of sulfided zinc ferrite sorbents were studied by Focht et al. (1986) and Woods et al. (1991). Single pellet experiments were performed in a TGA reactor by Focht et al. (1986) using various oxygen concentrations (2-10% in N_2) and O_2 - H_2O - N_2 mixtures in order to examine the effects of the reactive gas concentration and reactive mixture composition on the regeneration rates. Woods et al. (1991) regenerated sorbents at various temperatures (593-748°C) and pressures (1-20 atm). In both studies, zinc sulfate was found to form during the reaction of zinc sulfide with oxygen. Formation of zinc sulfate during regeneration is an undesirable side reaction because the sulfate decomposes in the initial stages of the next sulfidation cycle, producing high concentrations of sulfur gases (H_2S , COS , and SO_2) in the coal gas stream. Thermodynamic calculations were used to construct stability diagrams for the Zn - O - S and the Fe - Zn - O - S systems in the works of Dimitrov and Bonev (1986) and Krishnan et al. (1985), respectively. It is seen in the results of these two studies that formation of zinc sulfate is thermodynamically possible under the reaction conditions used in the regeneration of zinc oxide and zinc ferrite sorbents. Grindley (1988) tried to eliminate the problems associated with $ZnSO_4$ formation by including a reductive regeneration step in the sulfidation-regeneration cycle, during which the oxidatively regenerated sorbent was exposed to a reducing atmosphere.

In Sections 2 and 3, we investigated in detail the sulfidation in a TGA reactor of particles (53-350 μm) of two porous ZnO samples. Our experimental results were found to be in very good agreement with the predictions of the generalized random pore model of Yu and Sotirchos (1987). Moreover, the analysis of the experimental reactivity evolution data using the above mathematical model showed that the pore structure of the sorbent may strongly affect the observed sulfidation rates through the intraparticle diffusion coefficient, both its initial value and its evolution with the progress of the reaction. In this section, we discuss sulfidation-regeneration experiments that were carried out in a TGA reactor using two zinc oxides in particle form. The generalized random pore model is used to predict the performance of the sorbents during sulfidation and regeneration. The model considers that the void space in the interior of a porous solid is represented by a network of cylindrical pores that shrink during sulfidation, and thus may become plugged or inaccessible, and expand during regeneration. Samples of regenerated solids were prepared in a fixed-bed

reactor and the analysis of their pore structure was carried out using mercury porosimetry and nitrogen adsorption.

4.2. Materials and Pore Structure Data

Multiple sulfidation-regeneration experiments were carried out using two zinc oxide sorbents that we studied in Sections 2 and 3. Sorbents in particle form (53-62 and 297-350 μm) were used in all experiments. Samples of each ZnO sorbent were sulfided and regenerated in a fixed-bed reactor. The pore structure of the solid samples was characterized using mercury porosimetry and gas adsorption. About 0.7 g of each sample were placed in the reactor between two zones (2 cm in height) of quartz beads of about 1 mm in diameter. Particles of 53-62 μm were used in these experiments to minimize the reaction time. The fresh solids were heat-treated at 600°C under nitrogen flow for 30 min and they were then sulfided at the same temperature with 10,500 ppm H_2S diluted in nitrogen. The sulfided sorbents were regenerated at 650°C using a gas mixture of 2% oxygen diluted in nitrogen. The reactive gas flow rate for both reactions was 1,000 ml/min (at standard conditions). A gas sample was automatically injected every 3 or 5 min, during sulfidation or regeneration, respectively, in the gas chromatograph, in order to monitor the concentration of H_2S or SO_2 in the exit stream.

The pore structures of unreacted zinc oxides and of their sulfides were compared in Section 3. In this section, we compare the physical properties (surface area, pore size distribution, and pore volume) of the regenerated samples with those of the unreacted solids. The mercury porosimetry data obtained from the analysis of unreacted and regenerated 53-62 μm particles of the two solids are shown in Fig. 4.1. It should be noted that mercury intrusion volume for pore radius larger than about 1 μm is most probably due to invasion of the interparticle space. Hysteresis and mercury retention can be seen in both the unreacted and the regenerated samples. The pore volume of the sulfided sorbents is significantly lower than that of the unreacted sorbents (see Section 3), but the regenerated solids have about the same pore volume as the original solids. The ratio of the pore volumes (pore diameters in the range 100-10,000 Å) of regenerated and fresh (heat-treated) C7-2 sorbent is 98%, while the corresponding ratio for the G-72D sorbent is 91%. The

Figure 4.1 Mercury porosimetry data for unreacted (heat-treated) and regenerated sorbents.

Figure 4.2 Nitrogen isotherms for unreacted (heat-treated) and regenerated sorbents.

mercury intrusion and extrusion curves of the regenerated solids are shifted towards larger pore sizes relative to the corresponding curves of the unreacted solids. A similar behavior was also noticed in the pore size distributions of the sulfided solids (Fig. 3.18) prepared in a fixed-bed reactor, and this behavior was attributed to the effects of water vapor produced during sulfidation.

The nitrogen adsorption-desorption data of unreacted and regenerated sorbents are shown in Fig. 4.2. It is seen that sample C7-2 (unreacted and regenerated) has larger pore volume than sample G-72D, in agreement with the porosimetric data. The slope of the isotherms of the unreacted solids at P/P_0 values lower than 0.4 is almost the same, leading to BET surface areas of 26.57 and 27.72 m^2/g , for sample G-72D and C7-2, respectively. However, this is not the case for the regenerated solids, and thus surface areas of 12.81 and 17.38 m^2/g are estimated for the regenerated G-72D and C7-2 samples, respectively. The analysis of the sulfided solids gives lower surface areas (sample G-72D: 7.8 m^2/g ; sample C7-2: 13.78 m^2/g) than those of the regenerated sorbents. These results indicate that a large fraction of the initial surface area of each sorbent (52% for sample G-72D and 37% for sample C7-2) is lost during the sulfidation-regeneration cycle. A qualitatively similar change in the surface area of fresh, sulfided, and regenerated mixed metal oxide sorbents was measured by Tamhankar et al. (1986). The physical properties of fresh, sulfided, and regenerated zinc ferrite pellets were also measured by Sa et al. (1989), who found that the surface area loss (defined as the ratio between the difference of the surface areas of the unreacted and regenerated sorbent and that of the unreacted sorbent) was higher than the pore volume loss after regeneration of the sorbent at 650°C.

4.3. Experimental Reactivity Results

The experiments were carried out in a thermogravimetric system shown in Fig. 2.3. The reactive gas for the sulfidation experiments was 10,500 ppm H_2S diluted in nitrogen and for the regeneration experiments air. Pure nitrogen was used as inert gas and for diluting the reactive gases to the desired concentration. The solid reactant was uniformly spread on a circular quartz pan. Use of 2-3 mg of the sorbent and reactive gas flow of 200 ml/min were found to be adequate for differential operation of the reactor. Samples were

sulfided and regenerated isothermally. The fresh solids were heat-treated under nitrogen flow for 30 min in the beginning of each experiment. The heat-treated solids were reacted with 0.5% H_2S diluted in nitrogen at $600^\circ C$. As soon as sulfidation was completed the temperature was raised to $650^\circ C$ under nitrogen flow and the sulfided sorbents were reacted using 2% oxygen in nitrogen.

Sulfidation experiments with unreacted particles of sorbents G-72D and C7-2 were presented in Sections 2 and 3, where solid samples of various particle sizes (53-350 μm) were reacted with H_2S-N_2 mixtures of various H_2S concentrations in the temperature range $300-600^\circ C$. In this section we examine the regenerability of these sorbents and their desulfurization capacity after multiple sulfidation-regeneration cycles. Typical experimental data for multiple sulfidation-regeneration experiments are shown in Fig. 4.3 for 53-63 μm particles of sorbent G-72D. The sorbent was sulfided with 0.5% H_2S in N_2 and regenerated with 2% O_2 in N_2 at 600 and $650^\circ C$, respectively. The experimental data are presented as the ratio of the weight change during reaction to the initial ZnO weight in the sample. When complete sulfidation of ZnO takes place the ratio of final weight change to initial ZnO weight is equal to $(MW_{ZnS} - MW_{ZnO})/MW_{ZnO}$, with MW_i being the molecular weight of compound i . Obviously, the same weight change is expected when the sorbent is fully regenerated. The baseline change during the temperature rise from 600 to $650^\circ C$ (in a nitrogen atmosphere) was corrected using the results of blank experiments performed under identical conditions.

It is seen in Fig. 4.3 that the final weight of regenerated 53-62 μm particles of sorbent G-72D is larger than the weight of the unreacted solid. Moreover, the final weight change during sulfidation decreases from one cycle to the next, and in each cycle, the initial regeneration rate is lower than that at higher conversions. This behavior is most probably due to formation of zinc sulfate during the exposure of ZnS to the O_2-N_2 mixture. The reactions that may take place during regeneration are:

Figure 4.3 Multiple sulfidation-regeneration experiments for 53-62 μm particles of sorbent G-72D.

Figure 4.4 Multiple sulfidation-regeneration experiments for 297-350 μm particles of sorbent G-72D.

Formation of even small amounts of zinc sulfate influences significantly the interpretation of the weight change vs. time curves because while during regeneration (eq. (4.1)) a sulfur atom is replaced by an oxygen atom (weight loss), during sulfation (eq. (4.2)) four oxygen atoms are added to each zinc sulfide molecule (weight gain). The equilibrium constants for reactions (4.1) and (4.2) were calculated using the thermodynamic data of Barin and Knacke (1973). At 650°C the equilibrium constant of reaction (4.1) is $10^{21.1}$ and that of reaction (4.2) is $10^{26.6}$. However, if the reactive gas contains no SO_2 and the SO_2 produced by reaction (4.1) is removed from the reactor at such a rate that the SO_2 concentration in the system is practically zero, reaction (4.1) is expected to be thermodynamically more favored than reaction (4.2).

We can therefore limit the production of $ZnSO_4$ during the oxidation of zinc sulfide if we regenerate the sorbent under conditions that favor the decomposition reaction (eq. (4.3)). The thermal decomposition of reagent grade zinc sulfate was studied by Mu and Perlmutter (1981) and Narayan et al. (1988) using the thermogravimetric (TGA) and the differential thermal analysis (DTA) methods. According to those studies, the dissociation of anhydrous zinc sulfate to its oxide starts at about 600°C (under flow of inert gases), shows a 'plateau' region at about 720°C, corresponding to the formation of zinc oxysulfate ($ZnO \cdot 2ZnSO_4$), and reaches completion at about 850°C. These results explain the formation of large amounts of $ZnSO_4$ during reaction of ZnS with oxygen at low temperatures and suggest the use of high temperatures for successful regeneration. However, at temperatures above 700°C, we may have other undesirable phenomena like dissociation of zinc oxide and sintering of the porous solid (e.g., Gibson and Harrison (1980), Ranade and Harrison (1981), and Gangwal et al. (1989)). It was thus decided not to expose the sorbents used in this study at temperatures higher than 650°C. Other parameters influencing the rate of reaction (4.3) and the decomposition temperature were found to be the composition of the reactive gas – in the presence of oxygen the decomposition of $ZnSO_4$ started at higher temperatures (Narayan et al., 1988), while in the presence of CO this temperature decreased (Plewa and Steindor, 1989) – the presence of solid additives (Cr_2O_3 , Fe_2O_3 ,

and NiO (Mu and Perlmutter, 1981; Krishnan et al., 1985)), and the nature of the sample holder material (platinum, quartz, or ceramic (Narayan et al., 1988)).

Formation of zinc sulfate during the oxidative regeneration of ZnO -containing metal oxide sorbents was noticed in past experimental studies (e.g., Krishnan et al. (1985), Gangwal et al. (1989), Focht et al. (1986), and Woods et al. (1991)) performed in TGA reactors. The regeneration temperature and pressure, the composition of the reactive gas, and the chemical composition of the sorbents were found to affect the extent of reaction (4.2). A larger amount of sulfate was formed when the sorbents were regenerated at temperatures below $600^{\circ}C$ (Krishnan et al. 1985; Woods et al., 1991; Sa et al., 1990), and the produced $ZnSO_4$ could be decomposed either by exposing the regenerated sorbent at a reducing atmosphere (Grindley, 1988; Gangwal et al., 1989) or by increasing the regeneration temperature (Focht et al., 1986; Woods et al., 1991). An increase in the overall pressure led to formation of more $ZnSO_4$ for the same oxygen concentration (Woods et al., 1991), and more $ZnSO_4$ was formed in $ZnFe_2O_4-CuO$ sorbents than in zinc titanate sorbents of about the same initial pore volume and surface area (Gangwal et al., 1989). When SO_2 was added in the reactive gas mixture (Krishnan et al., 1985; Focht et al., 1986)), more $ZnSO_4$ was formed than during regeneration without SO_2 in the regeneration gas mixture.

Fig. 4.4 shows three sulfidation-regeneration cycles for 297-350 μm particles of sample G-72D. The reaction conditions were the same as those of Fig. 4.3, but the duration of each cycle for the large particles (3-5 hr) was larger than that of the small particles (1 hr) because intraparticle diffusional limitations decreased the reaction rates for the former particle size. During the first few minutes of all regeneration experiments of Fig. 4.4, an increase in the weight of the sorbent was noticed followed by a fast weight loss. A similar behavior was observed during regeneration of zinc ferrite pellets by Gangwal et al. (1989) and Woods et al. (1991). A possible explanation for this occurrence is the formation of $ZnSO_4$ in the beginning of the $ZnS-O_2$ reaction. The overall weight increase after the first cycle for 297-350 μm particles is almost constant, but the reaction rate decreases from one cycle to another, leading to lower sulfidation times.

Weight change vs. reaction time data for sample C7-2 are shown in Figs. 4.5 and 4.6

Figure 4.5 Multiple sulfidation-regeneration experiments for 53-62 μm particles of sorbent C7-2.

Figure 4.6 Multiple sulfidation-regeneration experiments for 297-350 μm particles of sorbent C7-2.

for 53-62 and 297-350 μm particles, respectively. The same reaction conditions were used for these experiments as for sample G-72D. The reaction rates of sorbent C7-2 for both particle sizes and all sulfidation-regeneration cycles are larger than the corresponding rates of sorbent G-72D. For instance, it is seen from Figs. 4.4 and 4.6 that three sulfidation-regeneration cycles were completed for the former sample in 3 hr, while within the same time period, the latter sample was sulfided and regenerated only once.

The compositional analysis of the two sorbents revealed the existence of small amounts of CaO in the unreacted solids in addition to ZnO and inert solids (0.016 g CaO/g ZnO for sorbent G-72D and 0.001 g CaO/g ZnO for sorbent C7-2). CaO is expected to react with H_2S and produce CaS , since thermodynamics favor the sulfidation of CaO for the reaction conditions of this study. (From the thermodynamic data of Barin and Knacke (1973), one finds that the equilibrium constant for sulfidation of CaO at 600°C is $10^{3.86}$, while that for sulfidation of ZnO at the same temperature is $10^{4.43}$.) Complete conversion of ZnO and CaO to their sulfides leads to a weight increase of 0.2005 and 0.1975 g per g of ZnO for samples G-72D and C7-2, respectively. However, when CaS is exposed to an oxidative atmosphere CaSO_4 may be formed in addition to CaO (Jalan, 1983), as it is expected from thermodynamic calculations for the CaS-O_2 system. (The equilibrium constant for formation of CaO from CaS at 650°C is $10^{21.68}$, while that for formation of CaSO_4 from CaS at the same temperature is $10^{34.45}$.) If we consider that during regeneration all ZnS reacts with O_2 to produce ZnO and that all CaS forms CaSO_4 , then the weight loss during regeneration of sorbents G-72D and C7-2 per initial g of ZnO should be 0.179 and 0.1964 g, respectively. However, as Figs. 4.3-4.6 show, smaller weight loss than these values is measured during the regeneration of the two solids, thus implying that formation of both ZnSO_4 and CaSO_4 takes place.

Comparison of the experimental data for the two samples used in this study (Figs. 4.3-4.6) shows that when sorbents G-72D and C7-2 are reacted with O_2 under identical reaction conditions they produce different amounts of ZnSO_4 , namely more ZnSO_4 is formed during the regeneration of sample G-72D than that during the regeneration of sample C7-2. The analysis of the sulfidation reactivity data of the two sorbents in Sections 2 and 3 showed that sorbent C7-2 has larger effective diffusivity than sorbent G-72D (see

Figure 4.7 Comparison of the conversion vs. time regeneration data for 297-350 μm of sample C7-2 using different O_2 concentrations (Dashed curves correspond to conversion vs. real time $\times$ % O_2 in the reactive mixture curves).

Fig. 3.17), and thus SO_2 escapes more easily from the interior pore space of the former solid. Results qualitatively similar to those of this study for the effects of the intraparticle diffusion coefficient on the extent of reaction (4.2) were obtained by Woods et al. (1991). Their experimental data showed that for a constant oxygen concentration, more zinc sulfate is formed during the regeneration of zinc ferrite pellets as the pressure increases. Since the intraparticle diffusion coefficient of the sulfided sorbent used in the experiments of Woods et al. (1991) is expected to depend on pressure – the sulfided sorbent had an average pore diameter of 2,000 Å – the production of larger amounts of zinc sulfate at high pressures could be attributed to the effects of increased intraparticle diffusion limitations on the extents of reactions (4.1) and (4.2).

In Fig. 4.7 we examine the effects of the oxygen concentration on the conversion vs. time curves of sample C7-2. Fresh 297-350 μm particles of this sample were sulfided and subsequently regenerated using 2.0 and 1.2 % O_2 in N_2 at 650°C. The experimental data vs. time are presented as solid curves in Fig. 4.7, while the dashed curves correspond to the same experimental results when they are plotted vs. the product of the real time and the % O_2 in the reactive gas. The conversion vs. normalized time (real time $\times$ % O_2) curves for different oxygen concentrations practically coincide, within experimental error, implying that the reaction of zinc sulfide with oxygen is of first-order with respect to the oxygen concentration. A linear relation was also found to exist between the initial reaction rates and the oxygen concentrations in the oxidation of porous zinc sulfides used in other studies (Prabhu, et al., 1984; Natesan and Philbrook, 1969), but the reaction rates of nonporous zinc sulfide (Cannon and Denbigh, 1957) were found to be proportional to the square root of the partial pressure of oxygen.

4.4. Model Predictions and Discussion

The generalized random pore model was applied previously to gas-solid reactions with solid product of larger molar volume than the solid reactant (e.g., sulfation of limestones (Zarkanitis et al., 1990) and sulfidation of fresh ZnO sorbents (Sections 2 and 3)). The performance of the model for gas-solid reactions with solid product of molar volume smaller than that of the solid reactant (regeneration of ZnO) has not been tested thus

far. We used the mercury intrusion data of unreacted heat-treated particles to describe the pore space in the interior of the porous particles, in accordance with the sulfidation studies of fresh sorbents. There are two adjustable parameters in the application of the mathematical model: the diffusion coefficient in the product layer (D_P) that depends on the temperature and the gas-solid system and the coordination number (z) (defined as the number of pores emanating from a site) that depends on the sorbent only. The values of these parameters were estimated fitting the model to the experimental data. The application of the mathematical model assumes that sulfidation and regeneration occur isothermally, although both reactions are exothermic, this is a reasonable assumption for a TGA arrangement and low concentrations of reactive gases.

The model predictions for pore structure evolution during sulfidation of the two sorbents used in this study were in agreement with the experimentally measured distributions (see Fig. 3.18). Hence, the predictions of the mathematical model for the pore size distributions of the sulfided and regenerated solids were used to describe structure evolution during reaction. During sulfidation pores shrink, and thus we may have closure of the small pores. As a result, formation of inaccessible pore space may take place when pores of finite length are used in the representation of the porous medium. In the application of the mathematical model, we consider that closed pores (pores plugged by solid product or pores with no access to the bulk gas phase through other pores) do not reappear as open pores during the regeneration process. Fig. 4.8 presents a two-dimensional analog of pore structure evolution during two sulfidations and one regeneration. Notice that because of pore plugging, the regenerated solid has different pore structure from the unreacted solid.

In Figs. 4.9 and 4.10, we compare the conversion vs. time curves of 53-62 and 297-350 μm particles of sample G-72D during three successive sulfidations. Notice that the regenerated particles do not reach complete conversion during sulfidation. This behavior and the different pore volumes of unreacted and regenerated samples for sample G-72D (see Fig. 4.1) imply formation of inaccessible pore volume or conversion of zinc to zinc sulfate. Formation of inaccessible pore space alone is not expected to prevent the solid from reaching complete conversion since the completely sulfided solid during the first cycle possesses a significant amount of open porosity. Therefore, it is believed that the main

Fresh Material

(A)

PARTIAL
SULFIDATION
(1st CYCLE)

(B) COMPLETE
SULFIDATION
(1st CYCLE)

(F) PARTIAL
SULFIDATION
(2nd CYCLE)

COMPLETE
SULFIDATION
(2nd CYCLE)

(C) PARTIAL
REGENERATION
(1st CYCLE)

(E)

COMPLETE
REGENERATION
(1st CYCLE)

(D)

Void Space

Oxide

Sulfide

Figure 4.8 Two dimensional analog of pore structure evolution during sulfidation and regeneration.

Figure 4.9 Conversion vs. time data for sulfidation of 53-62 μm unreacted and regenerated particles of sorbent G-72D.

Figure 4.10 Conversion vs. time data for sulfidation of 297-350 μm unreacted and regenerated particles of sorbent G-72D.

cause of incomplete conversion in subsequent cycles is the formation of zinc sulfate, which renders part of the zinc present in the original sorbent incapable of reacting with H_2S . Formation of sulfates ($ZnSO_4$ and $CaSO_4$) may also reduce the accessibility of the solid since the molar volume of $ZnSO_4$ ($43.2 \text{ cm}^3/\text{mol}$) is almost three times larger than that of ZnO ($14.7 \text{ cm}^3/\text{mol}$) and about two times larger than that of ZnS ($24.4 \text{ cm}^3/\text{mol}$). The sulfation of calcined limestones (Zarkanitis et al., 1990), where conversions lower than 30% were measured for porous particles of the same size (53-350 μm) and initial porosity (about 50%) as those of this study, is a typical example of a gas-solid reaction with solid product formation exhibiting incomplete conversion because of plugging and formation of inaccessible pore space.

The experimental data for sorbent C7-2 suggest that very small amounts of sulfates are produced during its regeneration. Therefore, we applied the mathematical model assuming complete regeneration and sulfidation of sorbent C7-2. In the comparison of the model predictions with the experimental data, we use solid lines for the theoretical results and distinct points for the experimental measurements. The conversion of the solid is computed from the weight change during reaction and the weight gain (or loss) that corresponds to complete conversion of ZnO to ZnS (or ZnS to ZnO in the regeneration reaction). Consequently, conversions computed from the experimental data of Figs. 4.5 and 4.6 do not necessarily reach unity at the completion of the reaction.

The comparison of experimental data and model predictions for sulfidation of 53-62 and 297-350 μm particles is given in Figs. 4.11 and 4.12, respectively. The mass transfer coefficient was estimated from standard correlations (eq. 3.48) for flow past spherical particles, and the reaction rate constant from the initial reaction rates using an analytical expression for the effectiveness factor of first-order reactions (eq. 3.45). The reaction rate constant, diffusion coefficient in the product layer, and coordination number of the pore network used to represent the pore space in the particles are listed in Table 4.1, along with the reaction conditions and the physical properties of the solid. The values of these parameters were the same in all sulfidation cycles shown in Figs. 4.11 and 4.12. Higher sulfidation rates were measured and predicted for the unreacted oxide than those for the regenerated solid. The model predicts that the regenerated 53-62 μm particles react slower

Figure 4.11 Comparison of the sulfidation data for 53-62 μm particles of sample C7-2 with the model predictions.

Figure 4.12 Comparison of the sulfidation data for 297-350 μm particles of sample C7-2 with the model predictions.

than unreacted particles of the same size in accordance with the experimental evidence. However, the predicted conversion vs. time curves for regenerated 297-350 μm particles are above the experimental data for all reaction times.

Table 4.1. Physical properties of sample C7-2, reaction conditions, and parameters used in the application of the mathematical model.

Reaction	Sulfidation	Regeneration
$v_s, cm^3/gmol$	23.9	33.6
Z	1.38	0.72
ν_A	1	1.5
z	∞	∞
Temperature, $^{\circ}C$	600	650
Pressure, atm	1	1
Mole fraction of reactive gas in N_2	0.005	0.02
$k_s, cm/s$	6×10^{-3}	2.2×10^{-4}
$D_P, cm^2/s$	10^{-8}	10^{-8}

The sensitivity analysis of the model predictions to the parameters involved in ZnO sulfidation that was performed in Section 2 showed that the behavior of large particles is primarily controlled by the value of the effective diffusivity in the porous particle. Closure of some small pore sizes affects more the behavior of the small particle sizes (53-62 μm) since the reaction rate of these particles depends more strongly on the local reactivity (intrinsic reaction and diffusion in the product layer) of the solid. Small pore closure affects weakly the diffusivity of a thoroughly interconnected pore network and, hence, the behavior of the large particles. When we used a finite coordination to describe the connectivity of the pore network after the first regeneration, we found that better agreement between model and experiment was obtained, as shown in Fig. 4.13. The data and parameters of Table 4.1 were used to obtain the results of Fig. 4.13, except the coordination number that

Figure 4.13 Comparison of the experimental data of sample C7-2 for the first two sulfidation cycles with the model predictions.

Figure 4.14 Comparison of the regeneration data for 53-62 μm particles of sample C7-2 with the model predictions.

Figure 4.15 Comparison of the regeneration data for 297-350 μm particles of sample C7-2 with the model predictions.

was set equal to 6. A possible explanation for the observed decrease of the connectivity of the pore network after regeneration is the closure of some pore segments because of formation of $ZnSO_4$.

The regeneration data of sorbent C7-2 are compared with the model predictions in Figs. 4.14 and 4.15 for particles of 53-62 and 297-350 μm , respectively. The same procedure as in the case of sulfidation was used to estimate the reaction rate constant. The reaction conditions, parameters, and physical properties of the sulfide used in the application of the model are listed in Table 4.1. The experimental data and the model predictions show weak dependence on the particle size, implying that the observed reaction rates are controlled by the local reactivity of the solid (intrinsic reaction rate and product layer diffusion). Moreover, our simulation results showed strong dependence of the predicted conversion vs. time trajectories on the reaction rate constant. This is not surprising since the average conversion of the particles shown in Figs. 4.14 and 4.15 is a linear function of the reaction time for conversions lower than about 80%. This observation is in agreement with the experimental results of Cannon and Denbigh (1957), who noticed that diffusional limitations in the oxide layer influenced the observed reaction rates only at high temperatures (above $830^\circ C$). Use of a finite coordination number (viz. $z = 6$) had a small effect on the model predictions for regeneration, since the regeneration rates under the reaction conditions used in this study are mostly controlled by the intrinsic kinetics.

4.5. Summary

Samples of two commercially available ZnO sorbents were sulfided and regenerated in a TGA reactor at 600 and $650^\circ C$, respectively. The desulfurization capacity of sorbent G-72D decreased after the first regeneration, and incomplete sulfidation took place after the first cycle, relative to the initial sorptive capacity of the solid, for both particle sizes used in this study (53-62 and 297-350 μm). This behavior is most probably caused by formation of zinc sulfate which reduces the amount of zinc available for H_2S removal. Sorbent C7-2 regenerated almost completely, and thus similar conversion vs. time curves were obtained during four sulfidation-regeneration cycles. Samples of the regenerated solids were prepared in a fixed-bed reactor and the analysis of their pore structure showed that

most of the initial pore volume is restored after regeneration, but a significant portion of the initial surface area is not recovered.

A detailed mathematical model for gas-solid reactions in porous solids, based on the generalized random pore model of Yu and Sotirchos (1987), was used to analyze the experimental data. The model could, in general, reproduce the experimental results, without using any adjustable parameters after the first sulfidation-regeneration cycle. However, use of a less interconnected pore network (smaller coordination number) during sulfidation of the regenerated sorbent than for the unreacted solid gave a better agreement between the sulfidation data of 297-350 μm particles and the model predictions. The analysis of the experimental results with the mathematical model showed that at the reaction conditions of our study, sulfidation is mostly influenced by diffusion, while the regeneration process is more strongly affected by the local reaction rate.

5. DEVELOPMENT OF A MATHEMATICAL MODEL FOR FIXED-BED DESULFURIZATION REACTORS

5.1. Introduction

A detailed mathematical model is presented here for the description of the dynamic behavior of fixed-bed reactors used for desulfurization of coal gas at high temperatures. Structural models of varying complexity and rigor, pore or grain based, are used to follow the evolution of the properties of the pore structure in the interior of the metal oxide pellets with the extent of the reaction. These structural models are based on the generalized random pore and grain models that have been developed by Sotirchos and Yu (1985, 1988) for gas-solid reactions with solid product. The desulfurization model is applied to the analysis of the transient behavior of fixed-bed reactors loaded with pellets of zinc oxide. Particular emphasis is placed on the investigation of the effects of the structural model used for representation of the pore structure of the pellets, as well as of the effects of the structural characteristics of the porous solid (internal surface area, porosity, and pore size distribution), on the breakthrough behavior of the reactor and, hence, on the utilization of the sorbent.

5.2. Development of the Mathematical Models

We consider a fixed-bed reactor packed with porous pellets consisting of metal oxide $M_{\nu_a}O_{\nu_b}$ and inert solid species. The coal gas entering the chemical reactor is treated as a dilute mixture of H_2S , which is assumed to be the primary contaminant. The existence of other sulfur-containing compounds in the coal gas is disregarded in the present analysis. The other gaseous species contained in the mixture are carbon monoxide, methane, hydrogen, carbon dioxide, nitrogen, and other organic compounds present at low concentrations. With the exception of H_2S which is assumed to react with the metal oxide according to the reaction equation

all other chemical species are considered to be inert with respect to it. With regard to our

application, therefore, the coal gas can be treated as a pseudobinary mixture of hydrogen sulfide and of an inert gaseous 'species.'

Because of the presence of small concentrations of gaseous reactant (H_2S) in the reactive mixture entering the chemical reactor, relatively low amounts of heat are released during the chemical reaction, and as result, heat effects associated with the occurrence of the desulfurization reaction can be neglected, and the fixed-bed reactor and the porous pellets may be treated as isothermal. The mathematical model for the reactor system, therefore, consists of equations describing the convective and diffusive transport of the gaseous reactant in the void space of the bed and the variation of the local average conversion of the solid with the position in the reactor, equations describing the diffusion of the gaseous species in the interior of each pellet, and finally equations describing the temporal and spatial evolution of the structural properties of the porous structure and of the conversion of the solid reactant in the interior of the pellets.

Equations for the Fixed-Bed

The material balance of hydrogen sulfide in the fixed-bed expressed in terms of its concentration, c_f , is written in the presence of mixing in the axial direction as (Froment and Bischoff, 1979)

$$\epsilon_b \frac{\partial c_f}{\partial t} = D_b \frac{\partial^2 c_f}{\partial z^2} - u \frac{\partial c_f}{\partial z} - \nu_b (1 - \epsilon_b) \bar{R}_v \quad (5.2)$$

$\bar{R}_v$ is the local reaction in the bed expressed in moles of metal oxide per unit of pellet volume and time, D_b is the axial dispersion coefficient of the gaseous reactant in the bed, ϵ_b is the porosity of the bed, and u is the superficial velocity.

The material balance for the solid reactant expressed in terms of its local average conversion in the bed, $\bar{\xi}$, is written as

$$\frac{\partial \bar{\xi}}{\partial t} = \frac{v_s}{1 - \epsilon_o} \bar{R}_v \quad (5.3)$$

where ϵ_o is the initial porosity of the pellets, and v_s is the 'molar' volume of the unreacted solid phase expressed as volume of solid phase per mole of solid reactant.

The Danckwerts boundary conditions (Danckwerts, 1953) are imposed on eq. (5.2), and it is assumed that the reactor is initially loaded with fresh (unreacted) pellets and

that the initial concentration of the gaseous reactant is equal to zero. In mathematical form we have that:

At $z = 0$:

$$-D_b \frac{\partial c_f}{\partial z} = u(c_i - c_f) \quad (5.4)$$

At $z = L$:

$$\frac{\partial c_f}{\partial z} = 0 \quad (5.5)$$

At $t = 0$:

$$c_f = 0 ; \bar{\xi} = 0 \quad (5.6a, b)$$

It is obvious from the form of eq. (5.2) that ϵ_b and D_b are treated as being invariant with time, a consequence of our tacit assumption that pellet size changes occurring as a result of the chemical reaction are insignificant. The length scale over which significant concentration differences are observed along the bed is assumed to be considerably larger than the average pellet size. This assumption enables us to consider that the local average reaction rate at some point in the bed equals at all times the average reaction rate of a pellet whose ambient conditions (concentration and temperature) are identical to those at the same point of the bed. Similarly, the local average conversion of the solid at some point of the bed can be considered equal to the average conversion of a pellet located at the same position.

If the pseudosteady state approximation is introduced in the material balance of the gaseous reactant in the interior of the pellets, the local average reaction rate in the bed, $\bar{R}_v$, for a first-order reaction - as it is the case considered in the present study - can be related to the reactant concentration in the bed by the relation

$$\bar{R}_v = \bar{k}_v(\bar{\xi})c_f \quad (5.7)$$

where $\bar{k}_v(\bar{\xi})$ is a local average reaction rate constant which depends only on the local average conversion in the bed or, equivalently, on the average conversion of the pellet. The validity of eq. (5.7) will become obvious after the model equations for the interior of the pellet and for the structure evolution problem are presented.

Equations for the Pellets

The material balance of hydrogen sulfide in the interior of the pellets expressed in terms of its concentration, c_p , has the form

$$\frac{\partial(\epsilon_p c_p)}{\partial t} = \frac{1}{r^s} \frac{\partial}{\partial r} (r^s D_e \frac{\partial c_p}{\partial r}) - \nu_b R_v \quad (5.8)$$

ϵ_p is the porosity, D_e is the effective diffusivity of hydrogen sulfide in the pellet, R_v is the local reaction rate expressed as moles of solid reactant per unit of pellet volume and time, and s is the shape factor of the pellet (0 for a slab, 1 for a cylinder, and 2 for a sphere). The material balance for the solid expressed in terms of the local conversion, ξ , is written

$$\frac{\partial \xi}{\partial t} = \frac{\nu_s}{1 - \epsilon_o} R_v \quad (5.9)$$

The following boundary and initial conditions are applied to eqs. (5.8) and (5.9):

$r = 0$:

$$\frac{\partial c_p}{\partial r} = 0 \quad (5.10)$$

$r = a$:

$$-D_e \frac{\partial c_p}{\partial r} = k_g (c_p - c_f) \quad (5.11)$$

$t = 0$:

$$c_p = 0 ; \bar{\xi} = 0 \quad (5.12a, b)$$

If the pseudosteady state approximation is applied in the diffusion equation of the gaseous reactant through the product layer surrounding the pores of the pellet (see the following section), the effective diffusivity in the porous structure, D_e , becomes a function of the local conversion, ξ , only. Moreover, the local reaction rate, R_v , may be related to the concentration in the pores, c_p , by the expression

$$R_v = k_v(\xi) c_p \quad (13)$$

where $k_v(\xi)$ is a volumetric reaction rate constant that depends only on the local conversion.

As it was mentioned in the previous section, the pseudosteady state approximation is also introduced in eq. (5.8) by assuming that changes occurring in the gas phase are

much faster than those occurring in the porous structure of the solid. Introducing the pseudosteady state approximation in eq. (5.8) and using eq. (5.13), eqs. (5.8)-(5.12) take the form:

$$\frac{1}{r^s} \frac{\partial}{\partial r} (r^s D_e(\xi) \frac{\partial y_p}{\partial r}) - \nu_b k_v(\xi) y_p = 0 \quad (5.14)$$

$$\frac{\partial \xi}{\partial t'} = c_f^* \frac{v_s}{(1 - \epsilon_o)} k_v(\xi) y_p \quad (5.15)$$

$r = 0$:

$$\frac{\partial y_p}{\partial r} = 0 \quad (5.16)$$

$r = a$:

$$-D_e \frac{\partial y_p}{\partial r} = k_g(y_p - 1) \quad (5.17)$$

$t' = 0$:

$$y_p = 0 ; \xi = 0 \quad (5.18a, b)$$

with

$$y_p = \frac{c_p}{c_f} ; t' = \frac{1}{c_f^*} \int_0^t c_f dt \quad (5.19a, b)$$

where c_f^* is a reference concentration.

It is clear from eqs. (5.14)-(5.18) that the state of the reacting single pellet system is a single function of the time variable t' defined in eq. (5.19b) or, equivalently (as eq. (5.15) implies), of the average conversion of the pellet. This approximation leads, as it will be explained in more detail later, to considerable simplification of the overall computational procedure since it enables us to solve the above set of equations independently of the equations for the fixed bed.

The average reaction rate per unit of pellet volume that is needed in the fixed-bed equations is computed by averaging eq. (5.13) over the pellet volume. By doing so and using eqs. (5.19a) and (5.7), the following expression is obtained for the average reaction rate constant of eq. (5.7):

$$\bar{k}_v(\bar{\xi}) = \frac{1}{a^{s+1}} \int_0^a k_v(\xi) y_p d(r^{s+1}) \quad (5.20)$$

with $\bar{\xi}$ obviously given by

$$\bar{\xi} = \frac{1}{a^{s+1}} \int_0^a \xi d(r^{s+1}) \quad (5.21)$$

Equations for the Structure Evolution Problem

The structural models used in this study to describe the evolution of the porous structure of the porous sorbent in the course of its reaction with H_2S are based on the random pore and random grain models that were developed by Sotirchos and Yu (1985, 1988). A brief description of these models will be given in the following paragraphs. Readers interested in more details are advised to consult the aforementioned research articles.

The random pore models consider that the initial pore space of the fresh sorbent can be described by a population of cylindrical capillaries of distributed or uniform size that are randomly distributed in the three-dimensional space. The population of cylinders is described by the distribution density $l_o(R_o)$ where $l_o(R_o)dR_o$ is the length of pores axes per unit volume that belong to capillaries with size in the range $[R_o, R_o + dR_o]$. Both discrete and continuous distributions of pore size were considered by Sotirchos and Yu (1985), but in this study we consider discrete distributions of pore size only, since in this case the numerical procedure involved in the solution of the model equations is considerably simpler.

For a discrete pore size distribution involving N initial pore sizes, $R_{o1}, R_{o2}, \dots, R_{oN}$, we obviously have that

$$l_o(R_o) = \sum_{i=1}^N l_{oi} \delta(R_o - R_{oi}) \quad (5.22)$$

where $\delta(\cdot)$ is the delta function, and l_{oi} is the length of pore axes of pores with size R_{oi} . The length distribution density, $l_o(R_o)$, can be determined from the experimentally measured pore size distribution of the solid which for a discrete pore size system obviously has the form

$$\epsilon_o(R_o) = \sum_{i=1}^N \epsilon_{oi} \delta(R_o - R_{oi}) \quad (5.23)$$

It can be shown (Gavalas, 1980 ; Sotirchos and Yu, 1985) that

$$l_{oi} = \frac{1}{\pi R_{oi}^2} \ln \left[\frac{1 - \sum_{j=i+1}^N \epsilon_{oj}}{1 - \sum_{j=i}^N \epsilon_{oj}} \right] \quad (5.24)$$

Notice that ϵ_{oi} represents the pore volume that belongs to capillaries of size R_{oi} including the overlap value with smaller capillaries.

The random grain models (Sotirchos and Yu, 1988) consider that the solid phase of the unreacted sorbent can be described by a population of grains (plate-like, cylindrical, or spherical) of distributed or uniform size which are randomly distributed in the three-dimensional space. The population of grains is described by the distribution density $n_o(R_o)$ where $n_o(R_o)dR_o$ is the number of grains per unit volume with size in the range $[R_o, R_o + dR_o]$. We consider cylindrical grains of average length $\bar{L}$ and slab grains of average surface area $\bar{A}$, where $\bar{L}$ and $\bar{A}$ are chosen arbitrarily. As in the case of the random pore models, in this study we will consider structures described by discrete grain size distributions. It is shown (Sotirchos and Yu, 1988) that the number density function

$$n_o(R_o) = \sum_{i=1}^N n_{oi} \delta(R_o - R_{oi}) \quad (5.25)$$

is related to the distribution density of the volume fraction of the solid phase

$$\phi_o(R_o) = \sum_{i=1}^N \phi_{oi} \delta(R_o - R_{oi}) \quad (5.26)$$

by the expression

$$n_{oi} = \frac{1}{f R_o^{s+1}} \ln \left[\frac{1 - \sum_{j=i+1}^N \phi_{oj}}{1 - \sum_{j=i}^N \phi_{oj}} \right] \quad (5.27)$$

ϕ_{oi} is the volume fraction of the solid phase that belong to grains with size R_{oi} including the overlapping volume with smaller grains, s is the shape factor of the grains, and f is their geometric factor ($4\pi/3$ for spheres, $\pi\bar{L}$ for cylinders, and $2\bar{A}$ for slabs).

After the metal oxide contained in the sorbent starts reacting with hydrogen sulfide, each pore or grain considered in the initial pore structure is covered by a layer of solid product, and the internal structure of the solid is, therefore, described by two receding surfaces defining the reacted solid-gas interface (pore surface) and the reacted-unreacted solid interface (reaction surface). In order to simplify the analysis of the pore structure problem, we assume that points of the reaction surface or of the pore surface of the same radius of curvature move with the same velocity (Sotirchos and Yu, 1985). Because of the above assumptions, the reaction and pore surfaces of the reacting structure can be described by populations of entities (pores or grains, depending on which model is used)

that are concentric to (spheres), coaxial to (cylinders), or have the same plane of symmetry (plates) as the entities used to represent the original structure. An entity of initial size R_{oi} , therefore, gives birth to two entities, one with size $R_{ri}(t)$ that is used to represent the reaction surface and one with size $R_{pi}(t)$ that represents the pore surface.

For grain structures R_{ri} represents the size of the unreacted core of the grain which obviously decreases monotonically with the conversion, and as a result, the unreacted core of a grain may vanish at some time instant. The unreacted cores of different size grains vanish at different times, with the cores of the smallest size grains vanishing first. For pore structures, R_{pi} represents the size of the capillary used to represent the pore structure of the porous medium which may increase or decrease with time depending on the stoichiometric volume ratio of the solid product-solid reactant system, $Z = v_P/v_S$, where v_P is the 'molar' volume of the reacted sorbent phase expressed as volume per mole of reactant. Obviously, for Z greater than 1.0 the produced solid product occupies more space than the solid reactant it replaces, and consequently R_{pi} increases with time, while the porosity of the solid decreases. It is assumed that a pore is completely plugged with solid product when its size reaches a critical threshold value, R_{pc} . Let ϵ_p be the porosity of the porous structure, and ϵ_r be the 'porosity' of the reaction surface structure, i.e., the volume fraction of void and reacted phase. The conversion of the solid is related to ϵ_p and ϵ_r by the relation

$$\xi = \frac{\epsilon_o - \epsilon_p}{(Z - 1)(1 - \epsilon_o)} = \frac{\epsilon_r - \epsilon_o}{1 - \epsilon_o} \quad (5.28a)$$

$$\epsilon_r = \epsilon_o + (\epsilon_o - \epsilon_p)/(Z - 1) \quad (5.28b)$$

By setting $\epsilon_p = 0$ in eq. (5.28a), one can find whether for given values of initial porosity, $\epsilon_o = 0$, and stoichiometric value ratio, Z , complete pore closure may take place before complete conversion is reached.

Equations for distributed pore growth

The equations for the variation of R_{ri} and R_{pi} with time are derived by solving the pseudosteady state diffusion equation of H_2S in the product layer surrounding pores of initial radius R_{oi} and by performing a mass balance on the solid material. For a first order reaction with intrinsic reaction rate given by $R_s = k_s c_{H_2S}$, we have that (Sotirchos and

Figure 5.1. Computer-generated section ($1\text{ }\mu\text{m}$ in side) of a random pore structure with discrete bimodal distribution of pore size. $\xi = 0.2$; $Z = 3$; $\epsilon_o = 0.5$; $\epsilon_{o1} = 0.25$; $R_{o1} = 200\text{ }\text{\AA}$ and $R_{o1} = 500\text{ }\text{\AA}$. (The hatched regions represent the solid product, and the cross-hatched the solid reactant.)

Yu, 1985, 1988)

$$\frac{dR_{ri}}{dt} = \frac{\lambda v_S k_s c_p}{1 + \frac{v_S k_s}{D_P} g_i} \quad (5.29)$$

$$\frac{dR_{pi}}{dt} = -\frac{dR_{ri}}{dt} \left[(Z - 1) \frac{\sigma_{ri}}{\sigma_{pi}} \right] \quad (5.30)$$

with

$$\frac{dg_i}{dt} = \lambda \left[\frac{dR_{ri}}{dt} - \frac{\sigma_{ri}}{\sigma_{pi}} \frac{dR_{pi}}{dt} \right] \quad (5.31)$$

$$R_{pi}(0) = R_{ri}(0) = R_{oi} ; g_i = 0 \quad (5.32a, b, c)$$

where $\lambda = \begin{cases} 1, & \text{for pores} \\ -1, & \text{for grains} \end{cases}$, σ_{ri} or σ_{pi} is the reaction or pore surface area per unit volume that belongs to entities with initial size R_{oi} , and D_P is the diffusion coefficient of H_2S in the product layer. When the unreacted core of a grain vanishes or a pore becomes plugged, the rates of change of R_{pi} and R_{ri} are set equal to zero.

For pore structures σ_{ri} , σ_{pi} , ϵ_p , and ϵ_r are given by the expressions (Sotirchos and Yu, 1985)

$$\sigma_{(r,p)i} = 2\pi(1 - \epsilon_{(r,p)})R_{(r,p)i}l_{oi} \quad (5.33)$$

$$\epsilon_{(r,p)} = 1 - \exp\left(-\pi \sum_{i=1}^N R_{(r,p)i}^2 l_{oi}\right) \quad (5.34)$$

For grain structures, on the other hand, we have that (Sotirchos and Yu, 1988)

$$\sigma_{(r,p)i} = (s + 1)f\epsilon_{(r,p)}R_{(r,p)i}^s n_{oi} \quad (5.35)$$

$$\epsilon_{(r,p)} = \exp\left[-f \sum_{i=1}^N R_{(r,p)i}^{s+1} n_{oi}\right] \quad (5.36)$$

Notice that ϵ_r may also be computed from ϵ_p using eq. (5.28b). In both cases, the reaction or pore surface area per unit volume is given by

$$S_{(r,p)} = \sum_{i=1}^N \sigma_{(r,p)i} \quad (5.37)$$

Fig. 5.1 presents a section (1 μm in side) of a random bimodal pore structure of 250 and 500 Å pores (initial radii) at 20% conversion, generated through computer simulation. The initial porosity of the structure of Fig. 5.1 is 0.5, the porosities of the two families of

pores are equal, and the stoichiometric volume ratio is 3. (The hatched regions represent the solid product, and the cross-hatched the solid reactant.)

Equations for uniform pore growth

The equation for the change of R_{ri} and R_{pi} with time can be considerably simplified if one assumes that all points of the pore and reaction surfaces that belong to active pores or grains move with the same velocity. We introduce two average growth variables q_r and q_p , where

$$R_{(r,p)i} = R_o + q_{(r,p)} \quad (5.38)$$

The equations for the change of q_r and q_p are derived by solving the pseudosteady state equation in the product layer of all active pores or grains and by performing a solid mass balance for all active pores or grains. We have that

$$\frac{dq_r}{dt} = \frac{\lambda v_s k_s c_p}{1 + \lambda \frac{v_s k_s}{D_p} S_{rm}(q_r) \int_{q_p}^{q_r} \frac{dq}{S_{(r,p)}(q)}} \quad (5.39)$$

$$\frac{dq_p}{dt} = -(Z - 1) \frac{S_{rm}(q_r)}{S_{pm}(q_p)} \frac{dq_r}{dt} \quad (5.40)$$

with

$$q_r(0) = q_p(0) = 0 \quad (5.41a, b)$$

$S_{(r,p)m}(q_r)$ is the reaction or pore surface area that belongs to entities with initial size greater than or equal to R_{om} where R_{om} is the least initial pore or grain size that is still active, i.e., the corresponding pore size is greater than the threshold for closure, R_{pc} , or the corresponding size of the unreacted core of the grain is finite. For pores $S_{(r,p)m}(q)$ is given by

$$S_{(r,p)m}(q) = 2\pi(1 - \epsilon_{(r,p)}) \left(\sum_{i=m}^N (R_{oi} + q) l_{oi} \right) \quad (5.42)$$

while for grains, we have that

$$S_{(r,p)m}(q) = (s + 1) f \epsilon_{(r,p)} \sum_{i=m}^N (R_{oi} + q)^s n_{oi} \quad (5.43)$$

Equations for D_e and k_u

The effective diffusivity for pore structures is obtained by averaging the diffusivity of H_2S in a single pore over the pore size distribution. For a discrete pore system we have that

$$D_e = \frac{1}{\eta} \sum_{i=m}^N D_A(R_{pi}) \epsilon_{pi} \quad (5.44)$$

with

$$\frac{1}{D_A(R_p)} = \frac{1}{D_{AB}} + \frac{1}{D_{KA}(R_p)} \quad (5.45)$$

m is the index of the least pore size that is still active, and ϵ_{pi} is the porosity of pores of size R_{pi} . The latter is given by (Sotirchos and Yu, 1985)

$$\epsilon_{pi} = \exp\left(-\pi \sum_{j=i+1}^N l_{oj} R_{pj}^2\right) - \exp\left(-\pi \sum_{j=i}^N l_{oj} R_{pj}^2\right) \quad (5.46)$$

For grain structures, the effective diffusivity is obtained from the expression

$$D_e = \frac{\epsilon_p}{\eta} D_A(\bar{R}_p) ; \bar{R}_p = \frac{2\epsilon_p}{S_p} \quad (5.47a, b)$$

The local reaction rate is obtained by averaging the reaction rate for a point of curvature R_{ri} over all points of the reaction surface. We have that

$$R_v = \frac{\lambda}{v_S} \sum_{i=m}^N \left(\frac{dR_{ri}}{dt}\right) \sigma_{ri} \quad (5.48)$$

Using eq. (5.29) or eqs. (5.38) and (5.39), we find that

$$k_v = k_s \sum_{i=m}^N \frac{2\pi(1-\epsilon_r)R_{ri}l_{oi}}{1 + \lambda \frac{\nu_A k_A}{D_p} g_i} \quad (5.49)$$

or

$$k_v = k_s \frac{S_{rm}(q_r)}{1 + \lambda \frac{\nu_A k_A}{D_p} S_{rm}(q_r) \int_{q_p}^{q_r} \frac{dq_r}{S_{(r,p)m}(q)}} \quad (5.50)$$

It is clear from the form of eqs. (5.29)-(5.31) or eqs. (5.39) and (5.40), that the results of the structural models can be rendered independent of the concentration in the pores by defining a new time variable given by $t'' = \frac{1}{c_p} \int_0^t c_p dt$ (compare with eq. (5.19b)). Therefore, the structural properties of the solid, and consequently D_e and k_v , depend only on the conversion of the solid and not on the concentration history of the gaseous reactant.

5.3. Computational Procedure

It must have become obvious from the form of the model equations presented in the previous section that the three submodels can be solved sequentially. We first solve the structural model and form a database for the variation of $k_v(\xi)$ and $D_e(\xi)$ with the local conversion in the pellet. The solution of the model for a single pellet then follows, and this helps us to construct a database for the variation of $\bar{k}_v(\bar{\xi})$ with the average conversion in the pellet, which is then used to solve the equations for the fixed bed.

The equations for the structural model are solved using a Gear-type integrator. The equations for the single pellet and the fixed-bed model are solved using cubic B-spline collocation (De Boor, 1978) to discretize the equations in space which is followed by temporal integration using a differential-algebraic equation solver for the pellet equations and a Gear type integrator for the fixed-bed equations. The values of $k_v(\xi)$ and $D_e(\xi)$ or $\bar{k}_v(\bar{\xi})$ at a given local or average conversion value are obtained through interpolation in the appropriate database using a procedure based on 'tensioned' splines (De Boor, 1978).

5.4. Application to ZnO and Discussion of the Results

The mathematical model that was developed in the previous sections is used here to study the behavior of a laboratory-scale desulfurization reactor packed with ZnO pellets of spherical shape. The values of the physical, pore structure, kinetic, and fixed-bed parameters employed in our computations are given in Table 5.1. The space velocity corresponding to the data of Table 5.1 is $3,600 \text{ hr}^{-1}$, while the Peclet number of 500 is based on an axial dispersion coefficient of $2.0 \times 10^{-5} \text{ m}^2/\text{s}$. The pseudobinary diffusion coefficient of H_2S in the mixture was estimated using the Chapman-Enskog equation for a binary mixture of H_2S and N_2 , while the tortuosity factor was taken equal to 3 for the cylindrical pore models (eq. (5.44)) and to 2 for the grain models (eq.(5.47)). The reaction rate constant given in Table 5.2 was estimated using initial reaction rate data for the $ZnO - H_2S$ reaction reported by Westmoreland et al. (1977) for the temperature range $350-750^\circ\text{C}$. Finally, the value chosen for the solid product layer diffusivity D_P was based on values obtained by various investigators by analyzing conversion vs. time data (e.g., Christman and Edgar (1983) and Sotirchos and Yu (1985)) for the diffusivity of SO_2

Figure 5.2. Effects of pseudosteady state assumption for the gaseous species in the interior of the pellets.

Figure 5.3. Breakthrough curves for solids with discrete pore size distribution (unimodal or bimodal) of the same porosity and internal surface area.

Figure 5.4. Sorbent utilization results for the solids of Fig. 5.3 for 10 ppm H_2S break-through concentration.

Figure 5.5. Variation of the effective diffusivity in the pellets of Fig. 5.3 with the local conversion.

in the $CaSO_4$ layer formed during sulfation of CaO particles.

Table 5.1. Physical, kinetic, reactor, and fixed-bed data used for ZnO .

$v_s = 14.87 \times 10^{-3} \text{ m}^3/\text{kmol}$	$D_p = 1.5 \times 10^{-12} \text{ m}^2/\text{s}$
$v_p = 24.12 \times 10^{-3} \text{ m}^3/\text{kmol}$	$\epsilon_o = 0.5$
$k_s = 2.5 \times 10^{-3} \text{ m/s}$	$\alpha = 1.5 \text{ mm}$
$T = 700^\circ\text{C}$	$x_{H_2S} = 3,000 \text{ ppm}$
$P_r = 500$	$L = 0.1 \text{ m}$
$u = 0.1 \text{ m/s}$	$\epsilon_b = 0.3$
$P = 1 \text{ atm}$	

Before we proceed with the investigation of the transient characteristics of the fixed-bed desulfurization reactor and their dependence on the submodels used to model the pore structure evolution process, it would be useful to examine the validity of the pseudosteady state assumption that was used to simplify the model equations and enable us to sequentially solve the three submodels that comprise the overall reactor model. Fig. 5.2 describes the transient response of the H_2S concentration and ZnO conversion profiles, obtained using the transient form of the material balance of hydrogen sulfide in the interior of the pellets (eq. (5.8)), in a partially reacted (41% average conversion) pellet of ZnO when this is exposed to the reactive mixture at time zero. It is seen that the concentration profile of H_2S reaches steady state in a relatively short time interval (about 4 ms) during which no noticeable change takes place in the conversion profile of the solid (dashed curves). This implies that the employment of the pseudosteady state assumption for the concentration profile of hydrogen sulfide in the pellets will have insignificant effects on the transient behavior of the reactor.

Effects of Distribution of Pore Size

Breakthrough curves for a fixed-bed desulfurization reactor packed with zinc oxide pellets of discrete unimodal or bimodal distribution of pore size are given in Fig. 5.3. The solids of Fig. 5.3 have the same initial porosity and internal surface area but are characterized by different distribution of porosity between small and large pores and different

Figure 5.6. Variation of the volumetric reaction rate constant in the pellets of Fig. 5.3 with the local conversion.

Figure 5.7. Variation of the average volumetric reaction rate constant in the pellets of Fig. 5.3 with the local conversion in the bed.

pore sizes. (The initial internal surface area of $1.9 \times 10^7 \text{ m}^2/\text{m}^3$ used in the computations corresponds to $7 \text{ m}^2/\text{g}$ for zinc oxide pellets of porosity 0.5 or to $10 \text{ m}^2/\text{g}$ for pellets of porosity 0.65.) Using the molar volumes of solid product and solid reactant of Table 5.1, we find that the stoichiometric molar volume ratio of the $\text{ZnO} - \text{ZnS}$ system is equal to 1.62. Introducing this value in eq. (5.19) shows that complete pore closure can take place only for initial porosities lower than 0.38. Complete utilization is therefore theoretically possible for the solids of Fig. 5.3; it corresponds to about $0.41 \text{ g H}_2\text{S}/\text{g ZnO}$. The corresponding values of sorbent utilization, expressed as $\text{g H}_2\text{S}/\text{g ZnO}$, to the results of Fig. 5.3 for 10 ppm breakthrough concentration are shown in Fig. 5.4. Notice that approximate values of sorbent utilization for breakthrough concentrations much smaller than the inlet stream concentration can be obtained directly from the breakthrough curves by dividing the breakthrough time by the reaction time for complete sorbent utilization and complete desulfurization of the gas stream (which, as it can be easily shown, is equal to about 7.25 days for the reactor and sorbent data of Table 5.1) and multiplying the result by the maximum sorbent utilization mentioned above.

The results of Figs. 5.3 and 5.4 indicate that the transient behavior of the reactor, and hence its breakthrough history, is strongly influenced by the type of the pore size distribution of the solid. In order to better understand the behavior of the various curves shown in Fig. 5.3, it is helpful to consider the variation of the local reaction rate constant $k_v(\xi)$ and of the effective diffusivity $D_e(\xi)$ with the local conversion in the interior of the pellets and the variation of the average reaction rate constant $\bar{k}_v(\bar{\xi})$ with the average conversion of the pellets. The respective curves are shown in Figs. 5.5, 5.6, and 5.7. As curves D and C of Fig. 5.5 show, introducing large pores in the initial pore structure of the pellets leads, as expected, to higher intraparticle effective diffusivities for all local conversion levels. It also slows down the decrease of the local reactivity of the pellet with the conversion (see curves D and C of Fig. 5.6). This behavior is a consequence of the fact that before pore closure starts to take place, the reaction surface area of a distributed pore structure is larger at all porosity levels than that of a unimodal structure of the same initial porosity and internal surface area. (This is always true for uniform pore growth, as it can be shown using eqs. (5.33) and (5.34).) These two effects together lead to higher

average reactivities (see Fig. 5.7) for the distributed pore size solid and, as a result, to larger breakthrough times and higher sorbent utilizations (compare cases D and C of Figs. 5.3 and 5.4).

Increasing the size of the large pores or their contribution to the total initial porosity of the pellets requires that the size of the small pores is decreased in order that the same values of initial surface area and porosity be maintained. The small pores may thus become completely plugged with solid product (since $Z > 1$) before complete conversion is reached, which happens to be the case with solids A and B of Figs. 5.3 and 5.4. It can be shown using eqs. (5.24), (5.28a), and (5.34) that the value of the conversion at which closure of the small pores takes place in a discrete, bimodal pore structure, ξ^* , is given for uniform pore growth by the expression

$$\xi^* = \frac{1}{Z-1} \left[\frac{(1-\varepsilon_{o2})^{(1-R_{o1}/R_{o2})^2}}{1-\varepsilon_o} - 1 \right] \quad (5.51)$$

As Fig. 5.6 shows, when closure of the small pores takes place, the local reactivity of the solid goes through a sharp decrease because the portion of the reaction surface area that is primarily accessed through the small pores ceases to participate in the reaction process. The slope of the effective diffusivity vs. local conversion curve (Fig. 5.5) also goes through an abrupt change at this conversion level since the conversion now changes only because of reaction in the large pores.

The large drop in the local reaction rate that takes place when the small pores close effects a fast decrease of the average reaction rate of the pellet with the average conversion (see Fig. 5.7). It should be pointed out that when concentration gradients exist in the interior of the pellets, closure of the small pores does not take place simultaneously over the entire pellet volume. As a result, no discontinuity appears in the variation of the average reactivity of the pellet with the average conversion. Despite the large drop in the local reaction rate when plugging of the small pores occurs, solid B exhibits the largest breakthrough time. This is not the case for solid A because small pore plugging takes place at a relatively low conversion (about 35%), causing the average reaction rate of pellets A to eventually become lower than that of the other distributed pore size solids (B and C) at about 50% conversion. Thus, notice that the sorbent utilization for solid A is considerably

Figure 5.8. Breakthrough curves for solids with discrete pore size distribution (unimodal or bimodal).

Figure 5.9. Concentration and conversion profiles in the reactor for solid B of Fig. 5.3.

lower than that for solid B, while an analogous observation applies to its breakthrough time.

Figs. 5.3 and 5.4 also demonstrate the effects of the assumption of uniform pore growth on the predictions of the desulfurization model. As Figs. 5.5 and 5.6 show the assumption of uniform pore growth leads to higher local reactivities but lower intraparticle effective diffusivities. Depending on the relative magnitudes of these effects, their combined action may bring about an increase or a decrease in the average reactivity of the porous solid pellets (see Fig. 5.7). The above behavior is due to the fact that when uniform pore growth (or shrinkage) is assumed, the thickness of the product layer that covers the small pores decreases for a given conversion level, while the product layer that covers the large pores becomes thicker. This implies higher local reactivities (which are basically controlled by the small pores) and lower effective diffusivities (which are controlled by the large pores) for solids reacting with uniform pore growth or shrinkage (see Figs. 5.5 and 5.6). For this reason, pore closure takes place at higher conversion levels when the assumption of uniform pore growth is used (cases A and B).

The distributed pore size solid C exhibits insignificant dependence of its local reactivity on the assumption of uniform pore growth, but its intraparticle diffusivity appears to be influenced noticeably (see Figs. 5.5 and 5.6). As a result, its average reaction rate for uniform pore growth is lower, and its breakthrough times smaller. Cases A and B, on the other hand, present a range of local conversion values, in the vicinity of the point where plugging of the small pores takes place, in which the local reaction rate is considerably higher for uniform pore growth. This eventually leads to higher average reactivities at intermediate and high average conversions (Fig. 5.7) and, therefore, to higher breakthrough times (Fig. 5.3). These observations are in qualitative agreement with conclusions derived from the application of the distributed pore model to limestone sulfation (Sotirchos and Yu, 1985). The effects of uniform or distributed pore growth are rather weak for all four cases considered in Figs. 5.3-5.7, and consequently, the uniform pore growth structural model may suffice for the study of the overall desulfurization reactor for most pore size distributions. This is a very important conclusion since considerably less numerical effort is required for the solution of the structural model of uniform pore growth; it practically

involves the solution of a single ordinary differential equation only.

More results on the effects of the pore size distribution of the solid are presented in Fig. 5.8, which again depicts breakthrough curves for fixed-bed reactors loaded with zinc oxide pellets of discrete, unimodal or bimodal pore size distribution. The initial porosity of the pellets is the same, 0.5, and equally distributed between small and large pores. The radius of the small pores is also the same for all solids, but the radius of the large pores, and consequently the internal surface area, is allowed to vary. Application of eq. (5.51) to the distributed pore size solids of Fig. 5.8 shows that solid B does not exhibit small pore closure, while the small pores of solids C and D are completely plugged by solid product at conversions 92 and 86% , respectively. It is seen that the solid with unimodal pore size distribution (A) presents the smallest breakthrough times and, hence, the smallest values of sorbent utilization. This behavior is primarily due to the fact that the resistance for diffusion in the interior of the pellets of solid A is considerably higher than that for the distributed pore size solids (compare with the results of Fig. 5.3). The limitations for mass transport in the pore structure decrease significantly by replacing some of the 400 Å pores with larger (1000 Å) pores (solid B), and as a result, a marked increase is observed in the breakthrough time in spite of the significant decrease of the internal surface area that accompanies the introduction of larger pores in the structure. The breakthrough time experiences a further increase as the size of the large pores is increased to 5,000 Å, but the solid with large pores of 10,000 Å in radius (solid D) exhibits breakthrough times that are lower than those of the other two solids with distributed pore size (curves B and C). The favorable effect of the decreasing diffusional limitations on the average reactivity of the pellets with increasing size of large pores is offset for solid D by the loss of reaction surface area caused by the plugging of the small pores with solid product.

Typical H_2S concentration and ZnO conversion profiles in the fixed bed are presented in Fig. 5.9 at time intervals of 1 day. The profiles shown are for a fixed bed loaded with pellets having discrete, bimodal pore size distribution (solid B of Fig. 5.3). As it was pointed out during the discussion of the results of Figs. 5.3-5.7, the small pores of the pellets of this solid are completely plugged with solid product at about 70% local conversion causing a significant drop in the local and average reactivity of the pellets at about the

Figure 5.10. Breakthrough curves for solids with discrete grain size distribution (unimodal or bimodal) of the same porosity and internal surface area.

Figure 5.11. Variation of the volumetric reaction rate constant in the pellets of Fig. 5.10 with the local conversion.

same value of local and average conversion, respectively (see Figs. 5.6 and 5.7). Thus notice that the conversion profiles in the bed (solid curves of Fig. 5.9) tend to level off at about 70% conversion.

Effects of Distribution of Grain Size

We now turn our attention to the investigation of the effects of the grain size distribution of the solid and of the assumption of uniform grain growth (or shrinkage) on the predictions of the fixed-bed desulfurization model. Breakthrough curves for fixed beds loaded with pellets of discrete, unimodal or bimodal grain size distribution (spherical grains) are given in Fig. 5.10. The three grain structures used in the figure have the same initial porosity and internal surface area, equal to those of the pore structures of Fig. 5.3. The variation of the local reactivity of the solids, expressed in terms of the volumetric reaction rate constant $k_v(\xi)$, with the local conversion is shown in Fig. 5.11. The breakthrough behavior of the reactor appears to be strongly influenced by the grain size distribution of the solid. In contrast with the results for pore structures (Fig. 5.3) where the breakthrough time of the fixed bed loaded with pellets of uniform pore size is the smallest, the solid with unimodal grain size distribution presents the greatest breakthrough time. The two types of porous structures behave differently mainly because the reaction surface area of a distributed grain structure is smaller at conversions greater than zero than that of a unimodal grain structure of the same initial porosity and internal surface area while, as mentioned before, the opposite is true for pore structures. For the same reason the local reactivity of distributed grain structures (see Fig. 5.11) is smaller than the reactivity of the uniform grain size solid. It should be pointed out that the solids with distributed grain size are also characterized by smaller effective diffusivities at nonzero conversions, a result of their larger pore surface areas (see eq. (5.47)).

The unreacted core of the small grains vanishes before complete (local) conversion is reached. The variation of the local reactivity with the conversion presents a discontinuity in its slope at the point where this happens (see Fig. 5.11). It can be shown using eqs. (5.27), (5.28a), and (5.36) that the unreacted core of the small grains in a discrete, bimodal

grain structure vanishes at conversion ξ^* given for uniform grain growth by the expression

$$\xi^* = \frac{(1 - \phi_{o2})^{(1-R_{o1}/R_{o2})^{n+1}} - \epsilon_o}{1 - \epsilon_o} \quad (5.52)$$

which predicts 60% and 82% conversion for solids A and B of Figs. 5.10 and 5.11. As seen in Fig. 5.11, the assumption of uniform grain growth delays the disappearance of the unreacted core of the small grains and leads to higher local reactivities, a result of higher surface areas. Despite this, however, the fixed beds loaded with pellets reacting with uniform grain growth present smaller breakthrough times. This is caused by the smaller diffusivities of the uniformly reacting grain structures which counterbalance the influence of the higher volumetric reaction rate constants (Fig. 5.11). Because of these two antagonistic factors, the effects of the assumption of uniform grain growth on the transient behavior of the desulfurization reactor were found to be weak for all grain size distributions considered. It can thus be argued that the much simpler structural model for uniformly reacting grain structures may satisfactorily be employed to describe the structural evolution of the pellets of the sorbent.

5.5. Summary and Concluding Remarks

A mathematical model was developed for the description of the transient behavior of noncatalytic fixed-bed reactors loaded with pellets of metal oxide sorbents and used for desulfurization of coal gas at high temperatures. The mathematical model encompasses three sets of differential and algebraic equations: for reaction and transport in the fixed bed, reaction and diffusion in the porous pellets, and structural evolution of the porous structure. By assuming pseudosteady state for the concentration of H_2S in the pellets and first-order dependence of the rate of the desulfurization reaction on it, it was possible to sequentially solve the three sets of equations, starting with the structural model and ending with the model for transport and reaction in the fixed bed. Detailed structural models of distributed pore or grain size, which can describe almost all phenomena encountered in gas-solid reactions with solid product, were used to simulate the evolution of the internal structure of the porous metal oxide in the course of its reaction with H_2S .

The developed mathematical models were used to study the transient behavior of

desulfurization reactors loaded with zinc oxide pellets. Our simulation computations primarily focused on the investigation of the effects of the pore or grain size distribution on the breakthrough behavior of the reactor. The results of our computations showed that the form of the pore or grain size distribution strongly influences the transient behavior of the desulfurization reactor and, consequently, its breakthrough time and sorbent utilization. For the same initial porosity and surface area, the solid with uniform pore size appears to present smaller breakthrough times and sorbent utilizations, while the opposite is observed for grain structures. However, the small pores of a sorbent with broad pore size distribution may be completely plugged by solid product and therefore inactivate the portion of the reaction surface area of the porous structure that is primarily accessed through these pores, causing a significant loss of sorptive capacity. Analogous observations were made for grain structures.

We also investigated the effects of the assumption of uniform (i.e., independent of the local radius of curvature) rate of reaction at the reacted-unreacted solid interface. Because of a number of antagonistic factors the overall effects of this assumption on the dynamic behavior of the reactor were found to be rather weak. We thus believe that use of the much simpler uniform pore or grain growth (or shrinkage) model will suffice for most types of pore size distribution.

5.6. Notation

Symbols that do not appear here are defined in the text.

a	radius of the pearticle
c	concentration of the reactant gas
k_g	mass transfer coefficient
k_v	local volumetric reaction rate constant (in the pellet)
$\bar{k}_v$	local volumetric reaction rate constant (in the bed)
$l(R)dR$	length per unit volume of axes of pores with radius in the range $[R, R + dR]$
L	length of the fixed bed
$n(R)dR$	number per unit volume of grains with size in the range $[R, R + dR]$
Pe	Peclet number (uL/D_p)

q	uniform growth or shrinkage variable
r	radial distance in a pellet
R	capillary or grain radius
R_0	grain size or radius at time $t = 0$
R_v	average local reaction rate, per unit volume
$\bar{R}_v$	average local reaction rate in the bed, per unit of pellet volume
S	internal surface area of a two-phase structure (m^2/m^3)
Sh	Sherwood number ($Sh = k_g a / D_e$)
t	time
v_i	specific molar volume of solid i
z	axial distance in the bed
Z	stoichiometric volume ratio (v_P/v_S of solid product and reactant)

Greek Letters

ϵ	porosity of a capillary or grain structure
$\epsilon(R)dR$	porosity due to pores with radius in the range $[R, R + dR]$
η	tortuosity factor
ν_b	stoichiometric coefficient of the gas
ξ	local conversion in the pellets
$\bar{\xi}$	average conversion of the pellets or local conversion in the bed
ϕ	volume fraction of the solid phase

Subscripts

$1, \dots, N$	refer to the i th pore or grain size of a discrete distribution
f	refers to the gas phase in the bed
o	refers to $t = 0$
p	refers to the pore surface or to the pore space
P	refers to the solid product
r	refers to the reaction surface
S	refers to the solid reactant

BIBLIOGRAPHY

Anderson, G.L., Berry, F.O., Gross, M.N., 1984, Development of a Hot Gas Cleanup System for Integrated Coal Desulfurization/ Molten Carbonate Fuel Cell Power Plants, DOE/MC/19403-1544.

Barin, I., Knacke, O., 1973, *Thermochemical Properties of Inorganic Substances*, Springer Verlag, Berlin.

Barrett, E.P., Joyner, L.G., Halenda, P.P., 1951, The Determination of Pore Volume and Area Distributions in Porous Substances. I. Computations from Nitrogen Isotherm, J. Amer. Chem. Soc., 73, 373-380.

Bartholomew, C.H., Agrawal, P.K., Katzer, J.R., 1982, Sulfur Poisoning of Metals, Adv. Catal., 31, 135-142.

Bird, R.B., Steward, W.E., Lightfoot, E.N., 1960, *Transport Phenomena*, John Wiley & Sons, NY.

Burganos, V.N., Sotirchos, S.V., 1987, Diffusion in Pore Networks: Effective Medium Theory and Smooth Field Approximation, AIChE J., 33, 1678-1689.

Caillet, D.A., Harrison, D.P., 1982, Structural Property Variations in the MnO-MnS System, Chem. Eng. Sci., 37, 625-636.

Cannon, K.J., Denbigh, K.G., 1957, Studies on Gas-Solid Reactions-I. The Oxidation Rate of Zinc Sulphide, Chem. Eng. Sci., 6, 145-154.

Christman, P.G., Edgar, T.F., 1983, Distributed Pore-Size Model for Sulfation of Limestone, AIChE J., 29, 388-395.

Danckwerts, P.V., Continuous Flow Systems, Chem. Eng. Sci., 2, 1 (1953).

De Boer, J.H., Linsen, B.G., Van Der Plas, T., Zondervan, G.J., 1965, Studies on Pore Systems in Catalysts. VII. Description of the Pore Dimensions of Carbon Blacks by the t-method, J. Catalysis, 4, 649-653.

De Boor, C., 1978, *A Practical Guide to Splines*, Springer-Verlag, NY.

Dimitrov, R., Bonev, I., 1986, Mechanism of Zinc Sulphide Oxidation, Thermochem. Acta, 106, 9-25.

Everett, D.H., 1979, in *Characterization of Porous Solids*, (eds. Gregg, S.J., Sing, K.S.W., Stoeckli, H.F.), Soc. Chem. Ind., London.

Fisher, M.E., Essam, J.W., 1961, Some Cluster Size and Percolation Problems, J. Math. Phys., 2, 606-619.

Focht, G.D., Sa, L.N., Ranade, P.V., Harrison, D.P., 1986, Structural Property Changes in Metal Oxide Hot Coal Gas Desulfurization Sorbents, Final Report, DE-AC21-84MC21166, Morgantown, WV.

Focht, G.D., Ranade, P.V., Harrison, D.P., 1988, High-Temperature Desulfurization Using

Zinc Ferrite: Reduction and Sulfidation Kinetics, Chem. Eng. Sci., 43, 3005-3013.

Froment, G.F., Bischoff, K.B., 1979, *Chemical Reactor Analysis and Design*, John Wiley & Sons, NY.

Furimsky, E., Yumura, M., 1986, Solids Adsorbents for Removal of Hydrogen Sulphide from Hot Gas, Science & Technology, 39, 163-172.

Gangwal, S.K., Stogner, J.M., Harkins, S.M., Bossart, S.J., 1989a, Testing of Novel Sorbents for H_2S Removal from Coal Gas, Environ. Progress, 8, 26-34.

Gangwal, S.K., Harkins, S.M., Woods, M.C., Jain, S.C., Boosart, S.J., 1989b, Bench-Scale Testing of High-Temperature Desulfurization Sorbents, Environ. Prog., 8, 265-269.

Gavalas, G.R., A Random Capillary Model with Application to Char Gasification at Chemically Controlled Rates, AIChE J., 26, 577 (1980).

Gibson, J.B., 1977, Kinetics of the Reaction of Hydrogen Sulfide and Carbonyl Sulfide with Spherical Zinc Oxide Particles, PhD Thesis, LSU and Agriculture Mechanical College, Louisiana.

Gibson, J.B., Harrison, D.P., 1980, The Reaction between Hydrogen Sulfide and Spherical Pellets of Zinc Oxide, Ind. Eng. Process Des. Dev., 19, 231-237.

Gregg, J.B., Sing, K.S.W., 1982, *Adsorption, Surface Area and Porosity*, 2nd ed., Academic Press, London.

Grindley, T., 1988, Sidestream Zinc Ferrite Regeneration Tests, DOE/ METC/6092, vol.1, 58-82.

Jalan, V., 1983, Studies Involving High Temperature Desulfurization/ Regeneration Reactions of Metal Oxides for Fuel Cell Development, DOE/MC/16021-1486.

Kimura, S., 1989, Oxidation Kinetics of Polycrystalline Zinc Sulfide Grains, AIChE J., 35, 339-342.

Kirkpatrick, S., 1971, Classical Transport in Disordered Media: Scaling and Effective Medium Theories, Phys. Rev. Lett., 27, 1722-1725.

Krishnan, G.N., Tong, G.T., Lamoreaux, R.H., Brittain, R.D., Wood, B.J., 1985, A Study of Sulfate Formation during Regeneration of Zinc Ferrite Sorbents, DOE/METC-85/6025, 6-18.

Larson, R.G., Morrow, N.R., 1981, Effects of Sample Size on Capillary Pressures in Porous Media, Powder Technol., 30, 123-138.

Lew, S., Jothimurugesan, K., Flytzani-Stephanopoulos, M., 1989, High-Temperature H_2S Removal from Fuel Gases by Regenerable Zinc Oxide-Titanium Dioxide Sorbents, Ind. Eng. Chem. Res., 28, 535-541.

Marsh, D.W., Urichson, D. L., 1985, Rate and Diffusional Studies of the Reaction of Calcium Oxide with Sulfur Dioxide, Chem. Eng. Sci., 40, 423-433.

- Mishra, B.K., Sharma, M.M., 1988, Measurement of Pore Size Distributions from Capillary Pressure Curves, *AIChE J.*, 34, 684-687.
- Mu, J., Perlmutter, D.D., 1981, Thermal Decomposition of Inorganic Sulfates and Their Hydrates, *Ind. Eng. Chem. Process Des. Dev.*, 20, 640-646.
- Narayan, R., Tabatabaie-Raissi, A., Antal, M.J., 1988, A Study of Zinc Sulfate Decomposition at Low Heating Rates, *Ind. Eng. Chem. Res.*, 27, 1050-1058.
- Natesan, K., Philbrook, W.O., 1969, Oxidation Kinetic Studies of Zinc Sulfide Pellets, *Trans. Met. Soc. AIME*, 245, 2243-2250.
- Patrick, V., Gavalas, G.R., Flytzani-Stephanopoulos, M., Jothimurugesan, K., 1989, High-Temperature Sulfidation-Regeneration of $\text{CuO-Al}_2\text{O}_3$ Sorbents, *Ind. Eng. Chem. Res.*, 28, 931-940.
- Plewa, J., Steindor, J., 1989, Investigation of Basic Zinc Sulfate Thermal Decomposition Under Nitrogen and Carbon Monoxide Atmosphere, *Thermochim. Acta*, 137, 281-291.
- Prabhu, G.M., Ulrichson, D.L., Pulsifer, A.H., 1984, Kinetics of the Oxidation of Zinc Sulfide, *Ind. Eng. Chem. Fundam.*, 23, 271-273.
- Ranade, P.V., Harrison, D.P., 1981, The Variable Property Grain Model Applied to the Zinc Oxide-Hydrogen Sulfide Reaction, *Chem. Eng. Sci.*, 36, 1079-1089.
- Rao, T.R., Kumar, R., 1982, An Experimental Study of Oxidation of Zinc Sulphide Pellets, *Chem. Eng. Sci.*, 37, 987-996.
- Reverberi, A., Ferraiolo, G., Peloso, A., 1966, Determinazione Sperimentale della Funzione di Distribuzione dei Macropori Cilindrici e 'ink bottles' in Sistemi Porosi, *Ann. Chim.*, 56, 1552-1561.
- Sa, L.N., Focht, G.D., Ranade, P.V., Harrison, D.P., 1989, High-Temperature Desulfurization Using Zinc Ferrite: Solid Structural Property Changes, *Chem. Eng. Sci.*, 44, 215-224.
- Sick, G., Schwerdtfeger, K., 1987, Hot Desulfurization of Coal Gas with Copper, *Met. Transactions B*, 18, 603-609.
- Smith, J.M., 1981, *Chemical Engineering Kinetics*, 3rd ed., McGraw-Hill, NY.
- Sotirchos, S.V., Yu, H.C., 1985, Mathematical Modelling of Gas-Solid Reactions with Solid Product, *Chem. Eng. Sci.*, 40, 2039-2052.
- Sotirchos, S.V., Yu, H.C., 1988, Overlapping Grain Models for Gas-Solid Reactions with Solid Product, *Ind. Eng. Chem. Res.*, 27, 836-845.
- Sotirchos, S.V., Zarkanitis, S., 1989, Pellet-Model Effects on Simulation Models for Fixed-Bed Desulfurization Reactors, *AIChE J.*, 35, 1137-1147.
- Svata, M., 1971, Determination of Pore Size and Shape Distribution from Porosimetric Hysteresis Curves, *Powder Technol.*, 5, 345-349.

- Tamhankar, S.S., Hasatani, M., Wen, C.Y., 1981, Kinetic Studies in the Reactions Involved in the Hot Gas Desulfurization Using a Regenerable Iron Oxide Sorbent-I Reduction and Sulfidation of Iron Oxide, Chem. Eng. Sci., 36, 1181-1191.
- Tamhankar, S.S., Bagajewicz, M., Gavalas, G.R., Sharma, P.K., Flytzani-Stephanopoulos, M., 1986, Mixed-Oxide Sorbents for High- Temperature Removal of Hydrogen Sulfide, Ind. Eng. Chem. Process Des. Dev., 25, 429-437.
- Westmoreland, P.R., Harrison, D.P., 1976, Evaluation of Candidate Solids for High-Temperature Desulfurization of Low-Btu Gases, Environ. Sci. Technol., 10, 659-661.
- Westmoreland, P.R., Gibson, J.B., Harrison, D.P., 1977, Comparative Kinetics of High-Temperature Reaction between H_2S and Selected Metal Oxides, Environ. Sci. Technol., 11, 488-491.
- Woods, M.C., Gangwal, S.K., Harrison, D.P., Jothimurugesan, K., 1991, Kinetics of the Reactions of Zinc Ferrite Sorbent in High-Temperature Coal Gas Desulfurization, Ind. Eng. Chem. Res., 30, 100-107.
- Yu, H.C., Sotirchos, S.V., 1987, A Generalized Pore Model for Gas-Solid Reactions Exhibiting Pore Closure, AIChE J., 33, 382-393.
- Yu, H. C., 1987, Theoretical and Experimental Studies on Gas-Solid Reactions with Solid Product, PhD. Thesis, University of Rochester, Rochester, NY.
- Yumura, M., Furimsky, E., 1985, Comparison of CaO , ZnO and Fe_2O_3 as H_2S Adsorbents at High Temperatures, Ind. Eng. Chem. Process Des. Dev., 24, 1165-1168.
- Zarkanitis, S., Sotirchos, S.V., 1989, Pore Structure and Particle Size Effects on Limestone Capacity for SO_2 Removal, AIChE J., 35, 821-830.
- Zarkanitis, S., 1990, Pore Structure and Reactivity Evolution during Limestone Sulfation, PhD. Thesis, University of Rochester, Rochester, NY.
- Zarkanitis, S.E., Efthimiadis, E.A., Sotirchos, S.V., 1990, Experimental Evaluation of a Class of Distributed Pore Size Models for Gas-Solid Reactions with Solid Product, Chem. Eng. Sci., 45, 2761-2768.

END

**DATE
FILMED**
6/18/92