NE E 13-5T

Supersedes RDT E 13-5T

June 1971

nuclear STANDARD

**FAST BREEDER REACTOR
FUEL PIN**

JANUARY 1984

*U. S. DEPARTMENT OF ENERGY
NUCLEAR ENERGY PROGRAMS*

Operated by
Westinghouse
Hanford Company
for the USDOE

A subsidiary of
Westinghouse Electric
Corporation

NE Standards Transmittal

A subsidiary of
Westinghouse Electric
Corporation

P. O. Box 1970
Richland, WA 99352

Hanford Engineering Development Laboratory

NE-E--13-5T-Rev.

DE93 011221

DISTRIBUTION	DATE January 12, 1984	NO. 277	
Lists 1 & 4	RETURN COMMENTS TO	TYPE SUBMISSION	TYPE ACTION
	CA Strand Westinghouse Hanford Company P. O. Box 1970 Richland, WA 99352	☐ 1. PRELIMINARY ☐ 2. DRAFT ☒ 3. TENTATIVE ☐ 4. FINAL ☒ 5. REVISION	☐ A. APPROVAL ☐ B. INFORMATION ☐ C. COMMENTS ☒ D. TRIAL USE ☐ E.
	NOT LATER THAN		
	NUMBER	DESCRIPTION	ACTION
	NE E 13-5T Fast Breeder Reactor Fuel Pins, January 1984. Supersedes June 1971 issue	C	
<p style="text-align: center;">DISCLAIMER</p> <p>This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.</p> <p style="text-align: right;">MASTER</p>			
DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED			

Handwritten signature

FOREWORD

This standard supersedes the June 1971 issue of RDT E 13-5T and incorporates those changes approved for publication in this revision. Because of extensive changes, the location of changes are not identified.

Significant changes that have been incorporated in this revision are summarized as follows:

1. Incorporation of FFTF fuel pin procurement experience.
2. Revisions of text to be more concise and more generally applicable by referencing the Ordering Data for certain technical specifications.
3. Deletion of certain quality assurance requirements that are adequately covered by reference to ANSI/ASME NQA-1, NE F 3-15T, and NE F 6-2T.
4. Updating of referenced standards.
5. Addition of Systeme International (SI) metric units.
6. Format changes in accordance with the current requirements for DOE Nuclear Energy Program Standards.

Editorial changes have been made to conform to the Department of Energy nuclear energy program decision to designate the RDT standards as NE standards rather than as NE(RDT). Some of the referenced standards are in the process of being updated and issued as NE standards. To minimize editorial corrections to this standard to correct reference to RDT standards to NE standards as they are issued, the corrections are being made prior to issuance of the RDT standards as NE. These changes are not identified.

FAST BREEDER REACTOR FUEL PIN

TABLE OF CONTENTS

	<u>Page</u>
1. SCOPE	1
1.1 Classification	1
1.2 Definitions	1
2. APPLICABLE DOCUMENTS	1
2.1 NE Standards	1
2.2 Federal Specifications	2
2.3 American Society for Testing and Materials (ASTM) Publications	2
2.4 American National Standards (ANSI)	3
2.5 Other Publications	3
2.6 Drawings	3
3. TECHNICAL REQUIREMENTS	3
3.1 General	3
3.2 Dimensions	3
3.3 Fuel Column	3
3.4 Uranium Dioxide Insulator/Blanket Pellets	5
3.5 Bonding Gas	5
3.6 Fuel Pin Integrity	6
3.7 Fuel Pin Closure Weld Requirements	6
3.8 Surface Condition	7
3.9 Identification	7
3.10 Workmanship	7
3.11 Process Qualification	8
3.12 Handling and Storage During Processing	8
3.13 Archive Samples	8
4. QUALITY ASSURANCE REQUIREMENTS	8
4.1 Quality Assurance Program Requirements	8
4.2 Quality Assurance Documentation	9
4.3 Inspection Requirements	9
4.4 Measuring and Test Equipment	9
4.5 Tolerance Limit Interpretation	17

	<u>Page</u>
5. PREPARATION FOR DELIVERY	17
5.1 Packaging	17
5.2 Shipping Container	17
5.3 Labeling	17
6. NOTES AND ORDERING DATA CHECKLIST	18
6.1 Ordering Data Checklist	18
6.2 Fuel Pin Fissile Content Determination	19

FAST BREEDER REACTOR FUEL PIN

1. SCOPE

This standard establishes the requirements for fuel pins to be used in FBR fuel assemblies. Fuel pins consist of mixed uranium-plutonium oxide fuel pellets clad with Type 316 stainless steel or other purchaser specified alloy steel.

1.1 Classification. This standard describes the basic requirements for FBR fuel pins. The purchaser will designate and specify the type(s) of fuel (e.g., enrichment) in the Ordering Data.

1.2 Definitions.

1.2.1 FBR. Fast Breeder Reactor.

1.2.2 Lot. Fuel pins processed consecutively and submitted for inspection at one time. For sampling acceptance of specific fuel pin characteristics, a lot may be defined as a population of fuel pins which would be expected to be homogeneous for the characteristic in question.

1.2.3 LTPD. Lot tolerance percent defective as defined in NE F 2-7.

1.2.4 β Risk. Purchaser risk as defined in NE F 2-7.

2. APPLICABLE DOCUMENTS

The following documents are a part of this standard to the extent specified in Sections 3 through 5. The issue of a document in effect on the date of invitation to bid, including any amendments or other published changes also in effect, shall be as specified in the Ordering Data. Where this standard appears to conflict with the requirements of a referenced document, such conflict shall be brought to the attention of the purchaser for resolution.

2.1 NE Standards.

NE E 13-6T	Fast Breeder Reactor Mixed Oxide Fuel Pellet
NE E 13-7T	Fast Breeder Reactor Uranium Dioxide Pellet
NE F 2-6T	Qualification and Control of Analytical Laboratories for Mixed Oxide Fuel Analysis
NE F 2-7T	Acceptance Sampling Plans

NE F 3-10T	Nondestructive Examination of Reactor Core Components
NE F 3-15T	Requirements for Inspection of Dimensional Characteristics
NE F 5-1T	Cleaning and Cleanliness Requirements for Nuclear Components
NE F 6-2T	Welding of Reactor Core Components and Test Assemblies
NE F 11-1T	Analytical Chemistry Methods for Mixed Oxide Fuel
NE F 11-3T	Analytical Chemistry Methods for Metallic Core Components
NE M 7-23T	Austenitic Stainless Steel Bar for Core Components
NE M 14-2T	Fuel and Control Assembly Tag Gas

2.2 Federal Specifications.

GGG-P-463	Plate, Surface (Granite)
-----------	--------------------------

2.3 American Society for Testing and Materials (ASTM) Publications.

ASTM A 240	Heat-Resisting Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Fusion-Welded Unfired Pressure Vessels
ASTM A 269	Seamless and Welded Austenitic Stainless Steel Tubing for General Service
ASTM A 276	Stainless and Heat-Resisting Steel Bars and Shapes
ASTM A 313	Chromium-Nickel Stainless and Heat-Resisting Steel Spring Wire
ASTM A 580	Stainless and Heat-Resisting Steel Wire
ASTM A 771	Austenitic Stainless Steel Tubing for Breeder Reactor Core Components
ASTM B 166	Nickel-Chromium-Iron Alloy (UNS N06600) Rod and Bar
ASTM E 3	Metallographic Specimens
ASTM E 29	Indicating Which Places of Figures Are to be Considered Significant in Specified Limiting Values

2.4 American National Standards (ANSI).

ANSI B46.1 Surface Texture

ANSI/ASME NQA-1 Quality Assurance Program Requirements for Nuclear Facilities

2.5 Other Publications. Other publications as specified in the Ordering Data.

2.6 Drawings. Drawings as specified in the Ordering Data.

3. TECHNICAL REQUIREMENTS

3.1 General. A fuel pin is a stainless steel (or other purchaser specified alloy) clad fuel pellet stack complete with end caps and internal hardware as specified in the Ordering Data.

3.1.1 Components and Materials. Fuel pin components shall be fabricated from materials meeting the requirements of the standards listed in Table 1 unless otherwise specified in the Ordering Data.

3.1.2 Gas Tagging. Fuel pins shall be gas tagged with gas meeting the requirements of NE M 14-2 as specified in the Ordering Data. The purchaser will supply details on the gas tagging method and specific tags required in the Ordering Data.

3.1.2.1 Tag Gas Weight. The weight of tag gas loaded into each fuel pin shall be as specified in the Ordering Data.

3.1.2.2 Tag Gas Release. Tag gas capsules shall be punctured to release the tag gas. Tag gas capsule puncture shall be verified in accordance with the requirements of Table 2, or if specified in the Ordering Data, the capsule puncturing process may be qualified. Qualification shall be maintained by periodic testing as specified in the Ordering Data.

3.2 Dimensions. Fuel pins and components thereof shall meet the dimensional requirements of the drawings specified in the Ordering Data.

3.3 Fuel Column. Fuel pins shall be loaded with the fuel pellets of the enrichment or type specified in the Ordering Data. The fuel pellets in the loaded pin shall meet the requirements of NE E 13-6 and the Ordering Data. A fuel column may be made up of pellets from more than one pellet lot provided the pellets are identified in accordance with 4.2.

3.3.1 Fissile Content. Fuel pin fissile content and average fuel pin fissile content shall meet the requirements specified in the Ordering Data. Determine fuel pin fissile content as specified in Table 2, Item 5. (See 6.2.)

Table 1. Driver Fuel Pin Components and Materials

Component	Product Form	Standard	Grade
Clad tube	tube	ASTM A 771 ^a	AISI 316 ^b
End caps	bar	NE M 7-23	AISI 316 ^b
Fuel pellets	sintered pressed powder	NE E 13-6	As specified in Ordering Data
Uranium dioxide pellets	sintered pressed powder	NE E 13-7	depleted uranium
Reflector (if specified)	bar	ASTM B 166	Inconel 600
Plenum spacer	tube	ASTM A 269	AISI 316
Hold down spring	wire	ASTM A 313	AISI 302
Tag gas capsule	tube sheet	ASTM A 269 ASTM A 240	AISI 316 AISI 316
Capsule penetrater	bar	ASTM A-276	AISI 410 ^c

^aWith additional requirements specified in the Ordering Data

^b20% cold worked

^cHeat treated for minimum hardness of RC-40

3.3.2 Americium Concentration. Isotopic analysis and date of analysis shall be provided for fuel pellets in each fuel pin to establish ²⁴¹Am and ²⁴¹Pu concentrations as specified in the Ordering Data.

3.3.3 Fuel Column Weight. Fuel column weight shall be determined as required by fissile content determination (3.3.1) and submitted to the purchaser. Column weighing accuracy shall be within ± 0.1 g at a 95% confidence level.

3.3.4 Column Length and Pellet Spacing. Fuel column length shall be as required on the drawing specified in the Ordering Data. Gaps greater than 0.015 in. (0.38 mm) appearing between pellets shall be closed unless material in the gap is identifiable as fuel. Fuel

pins with gaps that cannot be closed and that contain non-fuel material shall be rejected.

3.3.5 Volatiles Content. Fuel pellet volatiles content shall meet the following requirements. Fuel pellets for loading into fuel columns shall be inspected for gas content and moisture content in accordance with the requirements in Table 2, Item 8, or if specified in the Ordering Data, the pellet environment and handling process may be qualified in accordance with 3.11.

a. **Gas Content.** Exclusive of hydrogen and water, the average fuel pellet gas content shall not exceed $0.02 \text{ cm}^3 \text{ (STP)/g}$ ($2 \times 10^{-5} \text{ m}^3/\text{kg}$) fuel. The probability of accepting any given inspection lot of pins having a LTPD as high as 5 shall not exceed 0.05.

b. **Moisture Content.** The average fuel pellet moisture content in each finished pin shall not exceed $10 \text{ } \mu\text{g/g}$. The probability of accepting any given inspection lot of pins having a LTPD as high as 5 shall not exceed 0.05.

3.3.6 Fuel Oxygen-to-Metal Ratio. The average oxygen-to-heavy-metal (uranium plus plutonium) atom ratio of fuel pellets in each pin shall be 1.93:1 to 1.97:1 unless otherwise specified in the Ordering Data. The probability of accepting any given fuel pin lot having a LTPD as high as 5 shall not exceed a β of 0.05.

Fuel pellets for loading into fuel columns shall be inspected for oxygen-to-metal ratio in accordance with requirements of Table 2, Item 9, or if specified in the Ordering Data, the fuel pellet environment and handling process may be qualified in accordance with 3.11.

3.4 Uranium Dioxide Insulator/Blanket Pellets. Fuel pins shall be loaded with uranium dioxide insulator or blanket pellets meeting the requirements of NE 13-7 and the Ordering Data.

3.5 Bonding Gas. The fuel pin helium filling process shall be qualified to meet bonding gas purity and pressure requirements in accordance with 3.5.3.

3.5.1 Purity. The supplier shall establish with 95% confidence that:

1. The average helium plus hydrogen bonding gas concentration, exclusive of tag gas, within the fuel pins shall not be less than 98%.
2. The fuel pin bonding gas helium plus hydrogen concentration, exclusive of tag gas, is not less than 95% in at least 95% of the fuel pins.

3.5.2 Pressure. The pressure of the bonding gas in the finished fuel pin after closure shall be 1.0 ± 0.1 atm (100 ± 10 kPa) at room temperature.

3.5.3 Filling Process Qualification. Qualification shall be maintained by verification of compliance with the bonding gas purity and pressure requirements by periodic testing as specified in the Ordering Data. Any change in specified process parameters which potentially affects plenum gas helium purity or pressure shall require requalification.

3.6 Fuel Pin Integrity. The maximum leak rate of a finished fuel pin shall be 1×10^{-8} standard cm^3/s (1×10^{-14} m^3/s) of helium.

3.7 Fuel Pin Closure Weld Requirements. Welding procedure qualification, performance qualification, and production welding shall meet the requirements of NE F 6-2, Sections 1, 2, 3, and 4 unless otherwise specified in the Ordering Data.

3.7.1 Gas Tungsten Arc Weld (GTAW).

3.7.1.1 Throat Thickness. The throat thickness of the end cap to cladding weld shall be equal to or greater than 95% of the minimum specified cladding tube wall thickness unless otherwise specified in the Ordering Data.

3.7.1.2 Internal Weld Characteristics. The fusion and heat-affected zones of the welds shall meet all of the radiographic and metallographic examination requirements of NE F 6-2, Section 4.

3.7.1.3 Weld Diameter. The weld diameter shall not exceed the diameter shown on the drawing specified in the Ordering Data.

3.7.1.4 Finished Fuel Pin GTAW Closure Weld Surfaces. Finished fuel pin GTAW closure weld surfaces shall have no inclusions and none of the following unless otherwise specified in the Ordering Data:

1. Individual pits, mars, dents, scratches, gall marks, or other discontinuities greater than 0.0010 in. (0.025 mm) in depth.
2. Protrusions greater than 0.001 in. (0.03 mm) in height.

Weld ripple less than 0.002 in. (0.05 mm) from the highest to the lowest, shall not be considered a rejectable surface discontinuity.

3.7.2 Pulsed Magnetic Weld (PMW).

3.7.2.1 Weld Length. The minimum acceptable end plug to cladding axial weld length shall be as specified in the Ordering Data.

3.7.2.2 Weld Joint. There shall be no crevice at the outer end of the weld joint.

3.7.2.3 Finished Fuel Pin Cladding Surface. Finished fuel pin cladding surface over the closure weld shall have no visually apparent evidence of surface melting, no inclusions and none of the following unless otherwise specified in the Ordering Data:

1. Individual pits, mars, dents, scratches, gall marks, or other discontinuities greater than 0.0010 in. (0.025 mm) in depth.
2. Protrusions greater than 0.001 in. (0.03 mm) in height.

3.8 Surface Condition.

3.8.1 Cleanliness. Finished fuel pins and components thereof shall be clean and free of foreign material; e.g., free of grease, particulate matter, stains, and shall have a uniform appearance. Procedures and acceptance criteria for cleanliness and cleaning shall comply with NE F 5-1.

3.8.2 Residual Chloride and Fluoride. There shall be no more than 0.5 $\mu\text{g}/\text{in}^2$ (0.8 mg/m^2) each of chloride or fluoride on the surface of individual metallic components and fuel pins.

3.8.3 Radioactive Surface Contamination. There shall be no smearable radioactive surface contamination on a finished fuel pin as determined by the method in Table 2, Item 22.a. The maximum allowable fixed alpha radioactive surface contamination shall be 500 d/m in any 100 cm^2 .

3.9 Identification. Each fuel pin shall be identified with a legible serial number as specified in the Ordering Data. The method of identification shall be approved by the purchaser.

3.10 Workmanship. Completed fuel pins shall reflect high quality workmanship and shall be uniform in appearance.

3.10.1 Fuel Pin Surfaces. Fuel pin surfaces shall meet the following requirements:

a. Fuel pin cladding surfaces shall have none of the following unless otherwise specified in the Ordering Data:

1. Individual pits, mars, dents, scratches, gall marks, or other discontinuities greater than 0.0010 in. (0.025 mm) in depth.
2. Protrusions greater than 0.001 in. (0.03 mm) in height.
- b. End cap surfaces, except for closure weld surfaces, shall have no pits, mars, dents, scratches, gall marks, or other discontinuities greater than 0.005 in. (0.13 mm) in depth, greater than 0.150 in. (3.81 mm) in length (major dimension), or 0.010 in. (0.25 mm) in width (minor dimension).
- c. Weld surfaces shall meet the requirements of 3.7.1.4.
- d. Fuel pins shall bear no fingerprints or markings except as allowed in a., b. and c. above and as specified for fuel pin and component identification.

3.10.2 Foreign Materials. Any fuel pin containing foreign materials shall be rejected.

3.11 Process Qualification. The fuel pellet environment and handling process for producing fuel columns meeting volatiles content (3.3.5) and oxygen-to-metal ratio (3.3.6) requirements shall be demonstrated and may be qualified if specified in the Ordering Data. Qualification and verification of compliance with qualification requirements shall be as specified in the Ordering Data. Testing shall be in accordance with Table 2. Failure to meet verification of compliance shall require resampling and requalification. A change in enrichment or any change in the fuel fabrication process parameters which may affect fuel volatiles and oxygen-to-metal ratio shall require requalification.

3.12 Handling and Storage During Processing. Completed fuel pins and partially completed fuel pins shall be handled and stored in a manner to maintain conformance with this standard and individual component standards.

3.13 Archive Samples. Archive samples shall be taken as specified in the Ordering Data. The archive samples shall meet all requirements of this standard and Ordering Data. Quality assurance documentation specified in 4.2 shall be furnished with the archive samples. The archive samples shall be delivered to the purchaser as specified in the Ordering Data.

4. QUALITY ASSURANCE REQUIREMENTS

4.1 Quality Assurance Program Requirements. The supplier shall plan, establish, implement, and maintain a documented quality assurance program that fulfills the ANSI/ASME NQA-1 requirements specified in the Ordering Data.

4.2 Quality Assurance Documentation. The supplier is responsible for the preparation of all quality assurance documentation specified in this standard and in the Ordering Data. Records of all tests and examinations shall be kept complete. Quality verification records shall include:

1. The identity of each fuel pin (by serial number) and all materials/components thereof (by lot, heat, gas tag, etc.) as shown on the inspection/test and other quality status records.
2. Reports showing the results of all inspections and tests on fuel pins and component parts or materials thereof as required by this standard and applicable components or materials standards.
3. Other data which show the quality status of the fuel pin and component parts or materials.
4. Supplier's certification that each fuel pin meets all requirements of this standard and Ordering Data.

Quality verification records shall be furnished with the delivered fuel pins.

4.3 Inspection Requirements. Inspection requirements are listed in Table 2. Where "lot qualification" is listed as the inspection plan, the lot shall be accepted only when all of the required number of samples meet the referenced requirement. Where a sampling plan criterion is listed, the supplier shall establish the sampling plan. For those product characteristics requiring acceptance sampling, the supplier shall provide statistically significant evidence, based on his exhibited process capabilities and on the statistical acceptance sampling plan established for use, that the LTPD and β risk specified are not exceeded. Procedures for establishment of sample plans are given in NE F 2-7. Reference test methods are acceptable methods. Methods used shall be approved by the purchaser prior to use.

Where analytical methods are referenced in Table 2 for inspecting for conformance with chemical requirements, other analytical methods may be substituted for the reference test methods. Each analytical method used shall be qualified in accordance with NE F 2-6 and shall be approved by the purchaser prior to use.

4.4 Measuring and Test Equipment.

4.4.1 Environmental Controls. Measuring and test equipment and measurement standards shall be calibrated and utilized in an environment controlled to the extent necessary to assure continued measurements of required accuracy giving due consideration to temperature, humidity,

Table 2. Quality Conformance Inspection

Item	Rqmt.	Inspection Plan	Reference Test Method
1. Fuel pin component placement	3.1	Each fuel pin	Radiograph in accordance with NE F 3-10.
2. Gas tagging	3.1.2	As specified in Ordering Data	As specified in Ordering Data.
a. Tag gas weight	3.1.2.1	Each tag gas capsule	Weigh capsule on balance to nearest 0.1 mg. Determine gas weight by subtracting capsule tare weight from filled capsule weight.
b. Tag gas release	3.1.2.2	Each fuel pin or certification of process qualification	Radiograph in accordance with NE F 3-10. Flared or torn metal shall be evident on the radiograph.
3. Fuel pin dimensions			
a. Length	3.2	Each fuel pin	Standard gaging.
b. End Cap Concentricity	3.2	Each fuel pin	Standard gaging.
c. Straightness	3.2	Each fuel pin	Unless otherwise specified in the Ordering Data, finished fuel pins shall be inspected on a granite inspection table meeting Fed. Spec. GGG-P-463 (Grade B, Class 2) using feeler gages and allowing pin to be unrestrained.

(continued)

NUCLEAR
STANDARD

PAGE 10

NE
E 13-5T

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
4. Fuel column pellet enrichment (type)	3.3	Each fuel pin	Gamma scan.
5. Fissile content			
a. Fuel pin	3.3.1	Each fuel pin	Calculate by Equation 1 (6.2) using ^{239}Pu + ^{241}Pu concentration of the fuel pellet lot, and weight of the pellet stack. (Ref. NE E 13-6)
b. Average	3.3.1	Each type/order	If specified in the Ordering Data, determine average fissile content of all pins of a given type in order.
6. Fuel column weight	3.3.3	Each fuel pin	Balance: Weigh and record fuel pellet column weight before assembly (accuracy ± 0.1 g).
7. Fuel column length & pellet spacing	3.3.4	Each fuel pin	Measure column length and check for gaps between pellets after final pin closure with radiography having an accuracy of 0.02 in. (0.50 mm) for overall column length in accordance with NE F 3-10.

(continued)

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
8. Fuel column volatiles content			
a. Gas	3.3.5a	Sampling or certification of process qualification	In accordance with NE F 11-1. Sampling shall be after or immediately before pin loading and closure welding.
b. Moisture	3.3.5b	Sampling or certification of process qualification	In accordance with NE F 11-1. Sample and determine conformance as in 8(a) above.
9. Fuel oxygen-to-metal ratio	3.3.6	Sampling or certification of process qualification	In accordance with NE F 11-1. Sample and determine conformance as in 8(a) above.
10. Bonding gas			
a. Purity	3.5.1	Process qualification sampling	Mass spectrographic analysis of plenum gas.
b. Pressure	3.5.2	Process control	Pressure measurement of welding box atmosphere.
c. Filling process qualification	3.5.3	Process qualification sample	Mass spectrographic analysis of plenum gas.
		Process control	Monitor weld chamber gas purity and pressure.

(continued)

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
11. Fuel pin integrity	3.6	Each fuel pin	Test fuel pins with a helium leak detector sensitive to a leak of 5×10^{-9} std cm ³ /s of helium.
12. End cap to clad welding qualification	3.7	Sampling	Test and examine in accordance with NE F 6-2.
13. GTAW weld throat thickness			
a. Destructive test	3.7.1.1	Lot qualification based upon first & last weld sample taken in accordance with NE F 6-2.	Section, polish and etch welds. Observe and measure at 50X to 75X.
b. Nondestructive test	3.7.1.1	Each pin weld	Radiography in accordance with NE F 3-10.
14. GTAW internal weld			
a. Destructive test	3.7.1.2	Lot qualification based upon first & last weld sample taken in accordance with NE F 6-2.	Section, polish, and etch welds. Examine at 100X and photograph as specified in NE F 6-2. Specimen preparation shall be in accordance with ASTM E 3 and NE F 6-2.

(continued)

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
b. Nondestructive test	3.7.1.2	Each pin weld	Radiography in accordance with NE F 3-10.
15. Weld diameter	3.7.1.3	Each pin weld	Ring gage.
16. Finished GTAW surface	3.7.1.4	Each pin weld	Visual inspection at 1X. Fuel pin welds shall be examined against a white background and a light reading of no less than 200 foot candles (2150 lx) at the cladding surface.
17. PM weld length			
a. Destructive test	3.7.2.1	Lot qualification based upon first and last weld samples taken in accordance with NE F 6-2.	Section, polish and photograph at 10X in unetched condition. Etch and examine at 200X.
b. Nondestructive test	3.7.2.1	Each pin weld	Ultrasonic test in accordance with NE F 3-10.
18. Weld joint	3.7.2.2	Lot qualification based upon first and last weld samples taken in accordance with NE F 6-2.	Examine samples and photomicrographs taken for 17.a.

(continued)

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
19. Finished PMW closure surface	3.7.2.3	Each pin weld	Visual inspection at 1X.
20. Cleanliness	3.8.1	Each fuel pin	Visual inspection.
21. Residual chloride and fluoride			
a. Components	3.8.2	Lot qualification, three test samples per lot prior to fuel pin assembly.	In accordance with NE F 11-3.
b. Fuel pins	3.8.2	Lot qualification based upon tests from three randomly selected fuel pins per lot.	In accordance with NE F 11-3.
22. Radioactive surface contamination			
a. Smearable	3.8.3	Each fuel pin	Wipe pin lightly with tissue and survey tissue with an alpha scintillation counter with a minimum detection capability of 500 d/m.
b. Fixed	3.8.3	Each fuel pin	Survey fuel pins by using a calibrated alpha scintillation counter.

(continued)

Table 2. Quality Conformance Inspection (continued)

Item	Rqmt.	Inspection Plan	Reference Test Method
23. Identification	3.9	Each fuel pin	Visual inspection for readability, size, location, and correctness.
24. Workmanship			
a. Fuel pin surfaces	3.10.1	Each fuel pin	Visual inspection at 1X. Fuel pins shall be examined individually while suspended in a V-trough. Traverse the pin with a maximum 4 in. (100 mm) helical pattern, examining 100% of the fuel pin surface. Fuel pins shall be examined against a white background and a light reading of no less than 200 foot candles (2150 lx) at the cladding surface. The depth of discontinuities discovered at 1X shall be established through use of a depth measuring microscope or other method accurate to within ± 0.0001 in. (0.002 mm).
b. Foreign materials	3.10.2	Each fuel pin	Examine full length fuel pin radiograph prepared in accordance with NE F 3-10.

vibration, cleanliness, and other controllable factors affecting precision measurement. When applicable, compensating corrections shall be applied to calibration results obtained in an environment which departs from standard conditions.

4.4.2 Calibration. Measuring and testing equipment shall be calibrated as specified in Basic Requirement 12 and Supplement 12S-1 of ANSI/ASME NQA-1.

4.4.3 Accuracy. Unless otherwise specified in the Ordering Data or approved by the purchaser, determination shall be made with equipment meeting the requirements of NE F 3-15.

4.5 Tolerance Limit Interpretation.

4.5.1 Chemical Composition. For purposes of determining conformance with chemical composition requirements, an observed value or a calculated value shall be rounded off "to the nearest unit" in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding-off method of ASTM E 29.

4.5.2 Dimensional Requirements. The rounding-off method as defined in ASTM E 29 shall be used for determining conformance with dimensional requirements.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Fuel pins shall be packaged in a manner to maintain conformance to this standard. Fuel pins of different enrichments shall not be mixed in a package. Finished fuel pins are considered to have critical external surfaces and shall be packaged in accordance with the requirements of NE F 7-2. Use of desiccants, purge gas, or evacuation procedures is not required unless otherwise specified by the purchaser in the Ordering Data.

5.2 Shipping Container. The purchaser will supply shipping containers, inserts, and recording accelerometers to be attached to the shipping containers to monitor g forces incurred during shipment. The supplier shall ensure that accelerometers indicate less than 3 g at the time of shipment. The supplier shall provide a label on the container identifying which end contains the top end of the fuel pins.

5.3 Labeling. Each shipping container shall be clearly marked with the following information:

1. Purchase order number.
2. Type of fuel pin identified by drawing number, revision number, and part number.

3. Identification number to permit determining serial numbers of fuel pins in container.
4. Number of fuel pins.
5. Date packaged.
6. Fissile content.
7. Radiation level.

6. NOTES AND ORDERING DATA CHECKLIST

6.1 Ordering Data Checklist. The following technical and procurement data will be furnished by the purchaser. If not furnished with the purchase documents, the supplier shall request any necessary data before submitting his bid.

<u>Item</u>	<u>Refer to Paragraph</u>
1. Classification (type)	1.1
2. Applicable documents	2.0
3. Other Publications	2.5
4. Drawings	2.6
5. General requirements	3.1
6. Fuel pin components	3.1.1
7. Component materials	3.1.1
8. Gas tagging	3.1.2 and Table 2, Item 2
9. Weight of tag gas	3.1.2.1
10. Tag gas release process qualification	3.1.2.2
11. Dimensions	3.2 and Table 2, Item 3(c)
12. Fuel column, pellet type and additional requirements	3.3
13. Fuel pin fissile content	3.3.1
14. Average fuel pin fissile content	3.3.1
15. ^{241}Am and ^{241}Pu concentrations	3.3.2
16. Fuel column length	3.3.4
17. Volatiles - process qualification	3.3.5
18. Fuel oxygen-to-metal ratio and process qualification	3.3.6
19. UO_2 insulator/blanket pellet	3.4
20. Ratio of hydrogen to helium in bonding gas.	3.5.1
21. Bonding gas filling process qualification	3.5.3
22. Fuel pin closure weld requirements	3.7
23. Throat thickness (GTAW)	3.7.1.1
24. Weld Diameter (GTAW)	3.7.1.3
25. Minimum PMW length	3.7.2.1

26. Surface Defects (PMW)	3.7.2.3
27. Identification	3.9
28. Fuel pin surfaces	3.10.1
29. Process qualification	3.11
30. Archive samples	3.13
31. Specify ANSI/ASME NQA-1 quality assurance requirements	4.1
32. Accuracy	4.4.3
33. Packaging	5.1

6.2 Fuel Pin Fissile Content Determination. Conformance with the fuel pin fissile content requirement, 3.3.1 shall be established as follows:

Determine fuel pin fissile content by Equation 1.

$$F_2 = \frac{\bar{F}_1 W}{100} \quad (1)$$

where

F_2 = fuel pin fissile content in grams (^{239}Pu + ^{241}Pu) per fuel column.

F_1 = 100XY (fuel pellet fissile concentration expressed as percentage ^{239}Pu + ^{241}Pu in fuel)*

$\bar{F}_1$ = Average of F_1

X = Plutonium isotopic ratio (percentage ^{239}Pu + ^{241}Pu in Pu/100)*

Y = Plutonium fraction (percentage Pu in fuel/100)*

W = Weight of fuel column, g.

For the inherent variability of F_1 , calculate an acceptance criteria for individual fuel pins such that fuel pins having a fissile content varying more than ± 3.0% of nominal are rejected with 95% confidence.

*As defined in Para. 6.3 of NE E 13-6.