Prog:9262601

**Advanced Alternate Planar Geometry
Solid Oxide Fuel Cells**

3rd Interim Quarterly Technical Progress Report
July 1, 1988 to September 30, 1988

DOE/MC/25168--3289

DE93 013362

By

**Dave Prouse, S. Elangovan and A. Khandkar
Ceramatec, Inc.**

and

**Rich Donelson and Len Marianowski
Institute of Gas Technology**

Work Performed under
DoE Contract No: DE-AC 21-88MC25168

For

**Department of Energy
Morgantown Energy Technology Center
Morgantown, WV 26505**

By

**Ceramatec, Inc.
2425 South, 900 West
Salt Lake City, Utah, 84119.**

RECEIVED
MAY 20 1993
OSTI

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

yes

INTRODUCTION

This report documents the progress made during the quarter July - September 1988. During this quarter, technical discussions were initiated to discuss, in detail, the various tasks to be conducted during this development effort. These discussions were held at Ceramtec with IGT's Rich Donelson. The discussions also laid the framework for the management plan which was submitted. Ceramtec reviewed the activities under the different tasks and selected key electrode and seal compositions to be synthesized for out-of-cell testing and characterization. The materials were ordered. Technical discussions between Ceramtec and IGT were continued on the creep rig modification and other tasks to be conducted during this development effort. Below is detailed the progress at Ceramtec and IGT.

PROGRESS SUMMARY

Progress was made on the following tasks:

(1) Task 1.0: Cell Design Analysis:

It was decided that the cell be designed with reference to a small power application, eg. a 10 kW multi-family dwelling power source or a planar area of 12 in x 12 in. This was in keeping with realistic near term development goals.

IGT has developed a code for the design of the SOFC cell and has requested for materials property data and current fabrication limitations for cell components.

(2) Task 2.0: Program Liason and Test Facility Preparation:

Discussions continue on the test sample configuration so that the test facility can be readied for the creep tests.

(3) Tasks 3-6: Cell Component Fabrication Development:

Preliminary electrode material and glass sealing studies were started. Electrode matrix-electrolyte blanks were sintered for cross-section analyses.

Progress at Ceramatec

Task 3.0 Electrolyte Development and Fabrication:

Stabilized zirconia with 4 m/o yttria and 4 m/o ytterbia was cast into a thin tape using poly-vinyl butyrol binder system in an organic solvent, a tape casting slip formulation developed previously at Ceramatec. This tape was cast to a green thickness of 0.004 inch. A tape of the porous electrode matrix layer was also cast using a similar slip formulation. In both these tapes the solid loading was 60%. Two and three layers of the porous/dense and porous/dense/porous zirconia tapes respectively were laminated together at 110 °F at 100 psi. The two-layer laminate had a green thickness of about 0.022 inch and the three layer had a green thickness of about 0.036 inch. After firing the electrode matrix electrolyte composite had thicknesses of 0.019 inch and 0.029 inch for the two and three layer respectively. These were cross-sectioned for microstructural examination. SEM investigation of the microstructure will be carried out early in the next report period. Conductivity measurements are in progress and will be completed during the next report period. Preliminary trials on electrode material impregnation have begun (see Task 5.0). The results from this task will be used to develop a better electrode matrix structure. These trials are aimed at optimizing the impregnation process by changing the rheology of the electrode slurry, measuring the electrode performance characteristics in out of cell conductivity measurements as well as creep measurements and iteratively developing the porous electrode structure to obtain superior cell characteristics.

Task 4.0 Edge Seal Development and Fabrication:

Based upon Ceramatec's past experience, seal performance requirements had been identified. Briefly, the seal material should have the following characteristics:

- good wetting
- good bonding
- compatibility
- CTE match
- $T_g \approx 1100^\circ \text{C}$

The first two criteria, coupled with good microstructure (lack of recrystallization) assure hermeticity of the seal, the third and fourth criteria assures stability to fuel/oxidant gases as well as to thermal cycling and life and the last criterion assures ease of seal fabrication.

Based upon the above criteria, a glass candidate material has been selected for evaluation in sealing trials. Commercially available Zr-acetate cements (Aremco Ultratemp 571 and Ceramabond 516) have been ordered and will be tried as seal materials. It is anticipated that these cements may have to be modified by additions of zirconia powder in order to prevent migration of the seal material along the pore structure.

Literature on MDF cements is currently being evaluated. Based upon the survey MDF cements will be selected and materials will be ordered for seal trials.

The glass sealing material developed at Ceramatec has shown compatibility in in cell tests for a cumulative test time of approximately 900 hours and has been qualified for use in both air as well as fuel gas environment. The conventional method of application of this seal is to apply a bead of the material using a "slurry" which has a paste like consistency. The flow characteristics of this slurry are not adequate for impregnation into the porous matrix and therefore the slurry will have to diluted using thinning agents appropriate with the formulation. The preliminary trials are being conducted at the present time. The thinner is toluene, compatible with the organic base of the slurry. To develop the proper flow characteristics, empirical evaluation trials will have to be carried out .

A seal test rig has been constructed at Ceramatec for evaluation of the sealing technique as well as qualification of the seal materials. The schematic is shown in Figure 1. In this test, a test coupon is impregnated with the seal material and sealed onto a zirconia support tube. The support tube is then mounted in the rig as shown with the fuel gas flowing on the outside of the tube. Any leak is detected using the zirconia oxygen sensor. The sensor is exposed to air at the inner electrode and fuel at the outer electrode if no leak exists at the seal joint. Any leak at the seal introduces air and increases the oxygen activity

Schematic of a Seal Test Rig

at the outer electrode of the sensor which is detected by the sensitive high impedance digital voltmeter. The seal test rig was shown to have sensitivity to small fuel leaks by deliberately allowing a pin hole to form in the seal joint and monitoring the rise in the sensor potential. As soon as the other seal materials are received at Ceramtec, similar seal trials will be conducted.

5.0 Electrode Development and Fabrication

(a) Electronically Conducting ZrO_2 Based Electrode Materials

From a survey of the reported data of the properties of electrode candidate materials in this category, it appears that the best choice may be the 40/10/50 mol% composition in the three phase In_2O_3 - PrO_2 - ZrO_2 system. The materials for this composition have been ordered and will be evaluated as soon as they are available.

(b) Doped "p" type perovskites

For preliminary trials the "123" Y-Ba-Cu-oxide composition was obtained. This material was previously synthesized at Ceramtec under an in-house R&D program. This material will be made into a slurry and impregnated and tested. Trials have begun on using the conventional cathode material, Sr-doped $LaMnO_3$. This is expected to provide a useful baseline for further evaluation and comparison.

6.0 Interconnector Development and Fabrication:

IGT has been contacted and a concerted effort to identify alloys as well as vendors has begun at IGT.

Progress at IGT

Task 1.0 Cell Design Analysis:

Analysis of the actual cell design is to be carried out under this task. The main goal is to predict the relationships between configuration and performance of a SOFC using the planar-ribbed design. This should help identify the

optimum configuration of the cell. Ceramatec is to supply as much information regarding channel configuration, component thicknesses and electronic properties of the materials for use in this analysis.

The analysis developed so far calculates the pressure drop due to flow through channels, given a flow of gas necessary to create given electrical output (mA/cm²). The assumptions made include:

- Isothermal operation at 1000° C
- Medium BTU simulated coal gasifier effluent
- 85% fuel utilization

Electrical properties of the materials, as well as oxidant flow rates, are to be added next. The computer program will be modified to take into account the data concerning viable channel sizes, electrical properties of the materials, and component thicknesses which are supplied to IGT by Ceramatec.

Task 2.0 Program Liaison and Test Facility Preparation

This task involves the design and building of test equipment at IGT for the subsequent testing of SOFC components, which will be carried out under subsequent tasks. There are three types of tests to be carried out during the contract, these are:

- Creep testing of single or multiple SOFC components
- Cell sealing efficiency
- Complete cell tests.

During this reporting period, design work was carried for the Creep Test rig only. IGT has considerable amount of experience in creep testing components for the molten carbonate fuel cell (MCFC). However, creep testing of the SOFC present several challenges including different material and furnace requirements due to the higher test temperatures. Also, a smaller percent creep ($\Delta L/L$) is expected, thus requiring greater resolution for the measurement of deformation.

The creep test rig design incorporates a larger, rigid load rig similar to that used for 4" x 4" MCFC cell testing. Due to the high test temperatures, stainless steel and ceramics will be used for the test fixture. Creep will be measured using a differential transducer with the appropriate sensitivity. The fixture will then be housed in a retort to allow testing under different atmospheres.

Construction of the test rig will begin during the next reporting period, with testing under Task 7 to start after completion, and upon receipt of samples from Ceramatec.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

END

DATE
FILMED
6/11/93